



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.60	MT <b>Casing</b> Casing							
3.60	45.90	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Reddish brick. Some small intervals greenish-red and purple-red. 25% Fld phenos (3mm-10mm) and 10% lath phenos (3mmx5mm). Fld alteration is weak chlorite, weak potassic, weak albite, weak silice and medium epidote. Overall groundmass alteration is weak chlorite, weak sericite, weak carbonatation. Few quartz veins and fractures filled with chlorite. Trace of PY. Very weak mag.  HP, 3/09/10: "Popcorn" Syenite	3.60	4.80	D925465	1.20	0.154		0.154
			4.80	6.00	D925466	1.20	0.005		0.005
			6.00	7.70	D925467	1.70	0.054		0.054
			7.70	9.40	D925468	1.70	0.007		0.007
9.00	10.70	I2D POR; BRC <b>Syenite Porphyry Intrusive; Flow breccia</b> Brownish orange and green. Sections bleached. Fld strongly altered. Strong chlorite and epidote alteration. Intense oxydation. Weak Hematisation. Sharp upper and lower contact at 50 TCA. No mineralization.							
9.00	10.70	FRC <b>Fractured 50°</b> Fractured	9.40	10.30	D925470	0.90	0.025		0.025
9.55	10.15	VEI;60;Qz Cb;T;45°;Py00; <b>Vein 60 Quartz Carbonate Tension 45° Pyrite 0.01%</b> HP, 3/09/10: Cm scale laminated Qtz - Cb - sericitized wall rock slivers vein roughly @ 45 DTCA over 0.6 m; upper and lower contact zones foliated @ 45 DTCA; trace disseminated Py along wall rock sliver margins	10.30	12.00	D925471	1.70	0.028		0.028
			12.00	13.50	D925472	1.50	0.013		0.013
			13.50	15.00	D925473	1.50	0.050		0.050
			15.00	16.00	P002760	1.00	0.067		0.067
			16.00	17.00	D925474	1.00	0.109		0.109
			17.00	18.00	D925476	1.00	0.089		0.089
			18.00	19.00	P002761	1.00	0.023		0.023
			19.00	20.00	P002832	1.00	0.053		0.053
			20.00	21.50	D925477	1.50	0.105		0.105
21.50	24.40	Py00.2 <b>Pyrite 0.2%</b> HP, 3/09/10: Moderately fractured syenite; Qtz / Ser / Chl filled fractures; moderate wall rock silicification locally; trace disseminated Py locally	21.50	22.50	P002762	1.00	0.141		0.141
			22.50	23.50	P002763	1.00	0.073		0.073
			23.50	24.40	P002806	0.90	0.529		0.529
			24.40	25.70	D925478	1.30	0.258		0.258



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
45.90	51.00	<p>SY POR; SZ; FOL; CIS; I1N; FRA</p> <p><b>Syenite Porphyry Intrusive; Shear Zone; Foliation ; Sheared; Quartz Vein (or Qz stock work); Fractured</b></p> <p>Breccia. Greenish to greenish-gray-yellow. Highly fractured. Grey alteration around the fractures.</p> <p>Strong epidote ans sericite alteration and medium silica alteration. Matrix silica and smokey quartz veins.</p> <p>Phenos almost completely altered. Micro-fractures (5%) filled with chlorite. 3 to 5 % disseminated PY. Low mag</p> <p>HP, 3/09/10: Shear zone in (45.9-48.15); well developed foliation - parallel mm wide Qtz laminations (veins / injections) @ 40 DTCA; fairly sharp upper contact @ 55 DTCA, diffuse lower contact @ 55 DTCA; 50% cm-dm wide Qtz, minor Cb, intervals with/without cm scale sericitized wall rock intercalations; Qtz / silicified intervals locally brecciated; up to 1% disseminated Py locally, Py along foliation as well, up to 0.5% disseminated Aspy locally; (48.15-51.0) Moderately fractured - Chl / Cb / Qtz (Sil) coatings - veinlets, local cm scale silicification with up to 1% disseminated Py</p>	25.70	27.00	D925480	1.30	0.020	2.90	0.020
			27.00	28.50	D925481	1.50	0.148		0.148
			28.50	30.00	D925482	1.50	0.076		0.076
			30.00	31.50	D925483	1.50	0.030		0.030
			31.50	33.00	D925484	1.50	0.046		0.046
			33.00	34.00	P002764	1.00	<0.005		0.001
			34.00	35.00	P002765	1.00	0.028		0.028
			35.00	36.00	208724	1.00	0.332		0.332
			36.00	37.50	208725	1.50	0.173		0.173
			37.50	39.00	208726	1.50	0.415		0.415
			39.00	40.40	208727	1.40	0.166		0.166
			40.40	42.00	D925485	1.60	0.473		0.473
			42.00	43.50	P002924	1.50	0.321		0.321
			43.50	45.00	P002925	1.50	0.690		0.690
			45.00	46.00	P002766	1.00	0.419		0.419
			46.00	47.00	P002767	1.00	1.855		1.855
			47.00	47.90	P002769	0.90	3.000		2.900
47.90	49.00	P002770	1.10	1.090	1.090				
49.00	50.00	P002771	1.00	1.420	1.420				
50.00	51.00	P002772	1.00	0.493	0.493				
51.00	72.25	<p>SY POR; POR</p> <p><b>Syenite Porphyry Intrusive; Porphyric</b></p> <p>Reddish brick to reddish gray. 5-10% euhedral Fld phenos (3mm).</p>	51.00	52.00	P002773	1.00	0.058	0.058	
			52.00	53.00	208729	1.00	0.540	0.540	
			53.00	54.00	208731	1.00	0.416	0.416	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Weak chlorite and weak albite Fld alteration.	54.00	55.00	208732	1.00	0.014		0.014
		Overall groundmass alteration is weak chlorite, weak sericite, weak carbonatation. Small patches of epidote alteration.	55.00	56.00	208733	1.00	0.094		0.094
		Lots of fractures filled with silicate-carbonate material (25%) Few micro-fractures filled with chlorite. Trace of PY. No mag.	56.00	57.00	P002774	1.00	0.408		0.408
56.60	56.90	BX; BSF	57.00	58.00	P002775	1.00	0.013		0.013
		<b>Breccia 50°; Breccia Silicified zone</b>	58.00	59.00	P002776	1.00	0.023		0.023
		Breccia. Greenish-gray. Highly fractured. Grey alteration around the fractures. Medium silica alteration and weak epidote alteration. Matrix silica. Phenos are 3-4mm almost completely altered. 1-2% fine disseminated PY. Upper and lower contact sharp at 50 TCA.							
58.30	72.25	I2D; BX	59.00	60.00	P002777	1.00	0.006		0.006
		<b>Syenite; Breccia</b>							
		Breccia. Reddish brick. Highly fractured. Grey alteration around the fractures. Medium silica and carbonate alteration. Weak sericite alteration. Brownish-orange alteration (oxydation). Matrix silica. 20% Fld Phenos (2-3mm). Tr of fine disseminated PY.							
		HP, 3/09/10: Fractured to cm-dm scale intervals of clast-matrix supported breccia; mostly Cb, minor Qtz (Sil), in matrix							
60.00	88.00	FOL	60.00	61.00	P002778	1.00	<0.005		0.001
		<b>Foliation 50°</b>	61.00	62.00	P002779	1.00	<0.005		0.001
		Foliation	62.00	63.00	P002780	1.00	<0.005		0.001
		HP, 3/09/10: (75.9-76.3) Shear - fracture zone; medium brown-orange (Limonitized); abundant parallel fractures @ 45 DTCA; gradational contacts	63.00	64.00	P002781	1.00	<0.005		0.001
			64.00	65.00	P002782	1.00	<0.005		0.001
			65.00	66.00	D925486	1.00	<0.005		0.001
			66.00	67.50	D925487	1.50	0.006		0.006
			67.50	69.00	D925488	1.50	<0.005		0.001
			69.00	70.50	208734	1.50	0.084		0.084
			70.50	72.00	208735	1.50	0.011		0.011
			72.00	73.00	P002784	1.00	1.150		1.150
72.25	74.80	TZ; RUB	73.00	74.00	P002785	1.00	0.058		0.058
		<b>Transitional Zone; Banded</b>	74.00	75.00	P002786	1.00	0.128		0.128
		Transitional syenite zone. Greenish-gray, to brownish-orange. Bleached.							
		Intense chlorite alteration and medium sericite alteration. Band of							

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	chlorite. Fractures filled with silica-carbonate fluid. Fld highly altered. Breccia. Fine to medium grains. Trace to 0.5% PY. Lower contact at 50 TCA.							
	HP, 3/09/10: Shear - alteration zone; well developed foliation and 25% parallel to slightly cross cutting Qtz, minor Cb, veinlets - up to 5 cm wide veins @ 60-65 DTCA in (72.3-73.2); fairly sharp upper contact @ 60 DTCA marked by fairly abrupt change to strongly sericitized weakly foliated Syenite; (73.2-74.8) consists of strongly sericitized weakly foliated Syenite grading downhole into less sericitized brecciated Syenite, fairly abrupt end of sericitization at 74.8 m @ 45 DTCA							
74.80	168.10	SY POR; POR	75.00	76.00	P002787	1.00	0.366	0.366
		<b>Syenite Porphyry Intrusive; Porphyric</b>	76.00	77.00	P002788	1.00	0.011	0.011
		Purple to red-brown with intervals purple-orange and green. 20% euhedrals phenos (2-3mm) chloritised and 5% to 10% lath phenos.	77.00	78.00	P002789	1.00	<0.005	0.001
			78.00	79.00	P002790	1.00	<0.005	0.001
		Alteration : Weak Si, weak CL, weak ALB and weak SR.	79.00	80.00	P002791	1.00	<0.005	0.001
		Medium to coarse grains. Micro-fractures filled with Chlorite. Few veins filled with silica.	80.00	81.00	P002792	1.00	<0.005	0.001
		Hematization from 86.8m to 87.3m and 117.1 to 117.3. Strong epidotisation from 120.m to 121.6m and lots of fractures filled with chlorite (20%). Tr to 0.5 PY. Disseminated magnetite from 93m to 149m (mag+++).	81.00	82.00	P002793	1.00	<0.005	0.001
			82.00	83.00	P002794	1.00	<0.005	0.001
			83.00	84.00	P002795	1.00	<0.005	0.001
			84.00	85.00	P002796	1.00	<0.005	0.001
			85.00	86.00	P002797	1.00	<0.005	0.001
			86.00	87.00	P002798	1.00	<0.005	0.001
			87.00	88.00	P002799	1.00	0.005	0.005
			88.00	89.00	P002800	1.00	<0.005	0.001
			89.00	90.00	D925490	1.00	<0.005	0.001
			90.00	91.50	D925491	1.50	<0.005	0.001
			91.50	93.00	D925492	1.50	<0.005	0.001
74.80	75.30	I2D POR; BRC						
		<b>Syenite Porphyry Intrusive; Flow breccia</b>						
		Breccia. Purple. Highly fractured. Medium silica and carbonate alteration. Weak sericite alteration. Matrix silica. 10% Fld Phenos (2 mm). 2-3% (HP, up to 1% Py) of fine disseminated PY. Upper contact 60 TCA and lower contact 40 TCA.						
92.00	92.15	FRC						
		<b>Fractured</b>						
		Fractured and broken core (HP: Probably a mud seam; medium						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
93.00	105.00	orange-brown in color; Limonitized - oxidized; vuggy; some Qtz veining; sharp contacts @ 25 DTCA)  HP, 3/09/10: Medium brown-orange alteration (Limonite) halo in (91.55-92.2); distinct upper contact @ 25 DTCA, diffuse lower contact @ 45 DTCA  Pot10 <b>Potassic alteration 10</b> Potassic alteration	93.00	94.50	D925493	1.50	<0.005		0.001
			94.50	96.00	D925494	1.50	<0.005		0.001
			96.00	97.50	D925495	1.50	<0.005		0.001
			97.50	99.00	D925496	1.50	<0.005		0.001
			99.00	100.50	D925497	1.50	0.016		0.016
			100.50	102.00	D925498	1.50	0.036		0.036
			102.00	103.50	D925500	1.50	0.034		0.034
			103.50	105.00	D925501	1.50	0.070		0.070
			105.00	106.50	D925502	1.50	0.022		0.022
			106.50	108.00	D925503	1.50	0.019		0.019
			108.00	109.50	208747	1.50	0.096		0.096
			109.50	110.50	208748	1.00	0.036		0.036
			110.50	111.50	P002801	1.00	0.619		0.619
110.60	122.00	Epi40; Chl40 <b>Epidotisation 40; Chloritisation 40</b> Epidotisation+chloritisation							
110.90	111.00	VEI;10;Qz;T;55°;Py05; <b>Vein 10 Quartz Tension 55° Pyrite 5%</b> HP, 4/09/10: 10 cm wide Qtz vein - silicified zone @ 55 DTCA; 5% fine disseminated Py and Py in short stringers	111.50	113.00	208749	1.50	0.047		0.047
			113.00	114.00	D925504	1.00	<0.005		0.001
			114.00	115.50	D925505	1.50	0.012		0.012
			115.50	117.00	D925506	1.50	0.005		0.005
			117.00	118.00	P002802	1.00	0.008		0.008
			118.00	119.00	P002803	1.00	<0.005		0.001
			119.00	120.00	P002804	1.00	0.019		0.019
			120.00	121.00	P002805	1.00	0.046		0.046
			121.00	122.30	D925507	1.30	0.013		0.013
			122.30	123.80	D925508	1.50	<0.005		0.001
122.90	138.80	I2D; RUB; POR <b>Syenite; Banded; Porphyric</b> Green to dark green. Bleached. Fld completely altered (replaced)							

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	<p>by chlorite). Strong chlorite and epidote (HP, Sericite, not Epidote) alteration. Fractures filled with silica carbonate fluid. Few quartz vein (5%). Trace of Py. Gradational upper and lower contact.</p> <p>HP, 4/09/10: Upper interval change to 122.9 m (instead of 123.8 m); interval contains 7 pale- medium green sericitized moderately to well developed shear - alteration zones @ (122.9-123.1), (123.85-124.25), (125.4-126.2), (126.95-127.1), (128.0-130.5), (136.55-137.25), (137.9-138.8); generally with fairly sharp contacts or gradational contacts over a few cm; foliation generally @ 30-40 DTCA; (130.75-130.95) consists of badly broken core; some Syenite breccia (probably a fault breccia); Limonitized; Limonite alteration halo in (130.5-131.1) with sharp irregular contacts, upper @ 50 DTCA, lower @ 55 DTCA (Limonitization overprints Sericitization)</p>							
123.80	138.90							
	<p>Epi60; Chi90</p> <p><b>Epidotisation 60; Chloritisation 90</b></p> <p>Very strong epidotisation (HP, Sericitization, not Epidotization) and chloritisation</p>							
123.80	138.90	123.80	125.50	D925510	1.70	0.011		0.011
	<p><b>Foliation 50°</b></p> <p>Foliation</p>	125.50	126.50	P002807	1.00	0.018		0.018
125.97	126.03	126.50	128.00	D925511	1.50	0.007		0.007
	<p>VEI;6;Qz;T;55°;Py00;</p> <p><b>Vein 6 Tension 55° Pyrite 0%</b></p> <p>Quartz vein</p>	128.00	129.50	D925512	1.50	0.016		0.016
		129.50	130.40	D925513	0.90	<0.005		0.001
	<p>HP, 4/09/10: Vein is in (125.97-126.03) and not (125.97-127.03), @ 55 DTCA (not 70 DTCA); 0% Py (not 5% Py)</p>	130.40	131.20	D925514	0.80	0.005		0.005
		131.20	132.60	D925516	1.40	<0.005		0.001
		132.60	134.00	D925517	1.40	<0.005		0.001
		134.00	135.00	P002808	1.00	<0.005		0.001
		135.00	136.50	D925518	1.50	<0.005		0.001
		136.50	137.90	D925520	1.40	<0.005		0.001
		137.90	138.80	D925521	0.90	0.016		0.016
		138.80	140.50	D925522	1.70	<0.005		0.001
		140.50	142.20	D925523	1.70	0.014		0.014
		142.20	143.90	D925524	1.70	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
148.00	159.70	I2D; FOL  <b>Syenite; Foliation</b> Green to dark green. Fld completely altered (chlorite). Strong chlorite alteration. Strong potassic alteration from 157.9m to 159.5m. Plagio in veins. Weak albitisation. Fractures filled with silica carbonate fluid. Fractures filled with chlorite (20%) Albitisation. Few quartz vein (5%). Trace of Py. Gradational upper and lower contact.  HP, 4/09/10: Interval change, start at 148.0 m with parallel alignment of elongated phenocrysts @ 50 DTCA; moderate foliation with Chl-coated foliation planes and sericitization of wall rock starts at 151.5 m; (158.7-159.1) well developed foliation @ 55 DTCA; foliation and sericite alteration zone end at 159.7 m (151.5-165.0) 10% Qtz, lesser Cb, veinlets - up to 2 cm wide veins; (157.8-158.6) 50% Cb-Qtz veinlets - up to 7 cm wide veins (157.5-158.2) 0.5% disseminated <1 mm sized Py cubes, mostly in wall rock	143.90	145.50	D925525	1.60	0.005		0.005
			145.50	147.00	D925526	1.50	0.024		0.024
			147.00	148.50	D925527	1.50	<0.005		0.001
			148.50	150.00	D925528	1.50	<0.005		0.001
			150.00	151.50	D925530	1.50	<0.005		0.001
			151.50	153.00	D925531	1.50	0.006		0.006
			153.00	154.50	D925532	1.50	0.017		0.017
			154.50	156.00	D925533	1.50	0.020		0.020
			156.00	157.50	D925534	1.50	<0.005		0.001
			157.50	159.10	D925535	1.60	0.034		0.034
			159.10	160.50	D925536	1.40	<0.005		0.001
			160.50	161.70	D925537	1.20	0.008		0.008
161.70	162.40	BRE  <b>Breccia</b> HP, 4/09/10: Brecciated Syenite; 20% Cc-Qtz-Chl veinlets / matrix; Chl usually along veinlet / matrix margins; trace disseminated Py along veinlet / matrix margins	161.70	163.20	D925538	1.50	0.005		0.005
			163.20	164.80	D925540	1.60	0.040		0.040
			164.80	166.50	D925541	1.70	<0.005		0.001
			166.50	168.00	D925542	1.50	<0.005		0.001
168.00	175.00	FOL  <b>Foliation 60°</b> Foliation  HP, 4/09/10: Parallel alignment of Fspar phenocrysts	168.00	169.00	P002810	1.00	<0.005		0.001
168.10	180.70	SY POR; POR  <b>Syenite Porphyry Intrusive; Porphyric</b> Dark-purple to pink-purple. 40% euhedrals Fld phénos (2mm) and 10% (5-7mm). 20% lath Fld (3mmx5mm). Fld alteration : medium potassic and weak albite. Groundmass alteration : medium potassic, weak hematite, weak carbonate, weak sericite and weak chlorite. Foliated 60 TCA. Fractures filled with carbonate. Traces of Py. 2-3% Py from 172m to	169.00	170.00	D925543	1.00	<0.005		0.001
			170.00	171.00	D925544	1.00	<0.005		0.001
			171.00	172.00	P002811	1.00	<0.005		0.001
			172.00	173.00	D925545	1.00	<0.005		0.001
			173.00	174.00	D925546	1.00	<0.005		0.001
			174.00	175.00	P002812	1.00	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		180.7m. Disseminated magnetite. Mag+++	175.00	176.00	P002813	1.00	0.069		0.069
		HP, 4/09/10: Not a Syenite Lath Porphyry, just a Syenite Porphyry							
175.55	175.80	VEI;5;Qz Cc Cl;T;15°;; <b>Vein 5 Quartz Calcite Chlorite Tension 15°</b> HP, 4/09/10: 5 cm wide Qtz-Cc-Chl vein @ 15 DTCA; barren; 1% disseminated <2 mm sized Py cubes in overlying Syenite over 10 cm; 1-5% disseminated <2 mm sized Py cubes in underlying Syenite over 15 cm	176.00	177.00	P002814	1.00	0.005		0.005
176.10	176.50	Py01 <b>Pyrite 1%</b> HP, 4/09/10: 1% disseminated <2 mm sized Py cubes in highly fractured Syenite	177.00	178.00	P002815	1.00	<0.005		0.001
			178.00	179.00	P002816	1.00	<0.005		0.001
			179.00	180.00	P002817	1.00	<0.005		0.001
			180.00	181.00	P002818	1.00	<0.005		0.001
180.70	194.60	SY; FIN <b>Syenite; Fine grains</b> Greenish-pink to pinkish-gray. Fld completely altered. Alterations : Strong Chl, medium Si, medium Potassic. Foliation 40 TCA. Fractures (3%) filled with calcite and micro-fractures (1%) filled with chlorite. 10% magnetite disseminated. Mag+++	181.00	182.00	P002819	1.00	<0.005		0.001
			182.00	183.00	D925547	1.00	0.034		0.034
182.60	183.00	FRC <b>Fractured 05°</b> Fracture filled with calcite							
		HP, 4/09/10: Also Chl-coated hairline fractures							
183.00	188.00	FOL <b>Foliation 40°</b> Fol	183.00	184.50	D925548	1.50	0.182		0.182
			184.50	186.00	D925550	1.50	0.014		0.014
			186.00	187.50	D925551	1.50	<0.005		0.001
183.00	184.00	Py00.5 <b>Pyrite 0.5%</b> HP, 4/09/10: 0.5% disseminated <1 mm sized Py, mostly as cubes							
186.20	186.85	Chl80; Ser20 <b>Chloritisation 80; Sericitisation 20</b> Alteration							
186.85	210.00	Pot70 <b>Potassic alteration 70</b> Potassic alteration	187.50	189.00	D925552	1.50	<0.005		0.001
			189.00	190.60	D925553	1.60	<0.005		0.001
189.90	190.40	FOL; CIS	190.60	192.00	D925554	1.40	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Foliation 30°; Sheared</b>	192.00	193.50	D925556	1.50	<0.005		0.001
		HP, 4/09/10: Shear zone; moderately- well developed foliation @ 30 DTCA; gradational upper and lower contacts over a few cm; some <1 mm wide discontinuous foliation parallel Py-rich laminations; 10% foliation parallel to cross cutting Qtz-Cb veinlets, essentially barren or with Py along margins	193.50	195.00	D925557	1.50	<0.005		0.001
194.30	194.60	FOL; CIS							
		<b>Foliation 45°; Sheared</b>							
		HP, 4/09/10: Shear zone; moderately developed foliation @ 45 DTCA; 35% irregular mm wide discontinuous Cc-Qtz veinlets - aggregates, up to 1 cm wide Qtz-Cb veins; rare very fine disseminated Py; sharp upper and lower contacts							
194.60	314.10	SY POR; POR	195.00	196.50	D925558	1.50	0.015		0.015
		<b>Syenite Porphyry Intrusive; Porphyric</b>	196.50	198.00	D925560	1.50	<0.005		0.001
		Purple to purple-pink. 30% euhedrals phenos (2-5mm) chloritised.	198.00	199.50	D925561	1.50	<0.005		0.001
		Alteration : weak Si, medium CL, weak ALB, weak CARB, weak HEM, medium Potassic.	199.50	201.00	D925562	1.50	<0.005		0.001
		Strong silicate, chlorite, epidote alteration from 216m to 224.4m, from 225.8m to 229.35m and from 245.3 to 251.2m.	201.00	202.50	D925563	1.50	<0.005		0.001
			202.50	204.00	D925564	1.50	0.012		0.012
		Strong potassic alteration (patches) and strong SI alteration from 303m to 312m and Fld completely altered. Micro-fractures filled with epidote and Py, 5% Py	204.00	205.00	D925565	1.00	<0.005		0.001
		Medium to coarse grains. Micro-fractures (5%) filled with calcite. Tr to 1% PY. Disseminated magnetite (mag+++).	205.00	206.00	D925566	1.00	<0.005		0.001
206.00	207.00	Py01; Cp00	206.00	207.00	P002820	1.00	0.146		0.146
		<b>Pyrite 1%; Chalcopyrite 0%</b>	207.00	208.00	P002821	1.00	0.081		0.081
		HP, 5/09/10: 1% disseminated <1 mm sized Py cubes in lower 15 cm of interval; one 2 mm long Cpy (resembles VG) grain in a Qtz-Cb veinlet as well	208.00	209.70	D925567	1.70	<0.005		0.001
			209.70	210.70	D925568	1.00	0.053		0.053
210.00	210.30	VEI;25;Qz Cc Cl Cb;T;50°;Py00.5;	210.70	212.00	D925570	1.30	0.017		0.017
		<b>Vein 25 Quartz Calcite Chlorite Carbonate Tension</b>	212.00	213.50	D925571	1.50	<0.005		0.001
		<b>50° Pyrite 0.5%</b>	213.50	215.00	D925572	1.50	0.005		0.005
		HP, 5/09/10: 25 cm wide irregularly laminated Qtz-Cc-Chl-Cb vein @ roughly 50 DTCA; some wall rock inclusions; up to 1% disseminated <1 mm sized Py, mostly as cubes, in wall rock and along margins of wall rock inclusions	215.00	216.00	208736	1.00	0.008		0.008
215.90	219.50	FOL; CIS							
		<b>Foliation 35°; Sheared</b>							
		fol							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
216.00	224.40	<p>HP, 5/09/10: Interval change; shear zone; well developed foliation @ 35 DTCA; strongly sericitized and chloritized; locally up to 2% disseminated Py, mostly as &lt;1 mm sized cubes; 10% Qtz, lesser Cb, veinlets - one up to 14 cm wide vein, essentially barren or with Py along margins locally; some Py-Aspy stringers in (218.0-219.0); gradational upper and lower contacts</p> <p>Epi60; Ser40; Chl60; Sil30</p> <p><b>Epidotisation 60; Sericitisation 40; Chloritisation 60; Silicification 30</b></p> <p>Alteration</p>	216.00	217.00	208737	1.00	0.097		0.097
			217.00	218.00	208738	1.00	0.093		0.093
			218.00	219.00	P002822	1.00	0.881		0.881
			219.00	220.50	208739	1.50	0.151		0.151
		HP, 5/09/10: Chloritization, sericitization; no epidotization	220.50	222.00	208741	1.50	0.012		0.012
			222.00	223.00	208742	1.00	0.008		0.008
222.80	228.60	<p>FOL; CIS</p> <p><b>Foliation 55°; Sheared</b></p> <p>HP, 5/09/10: Shear zone; well developed foliation @ 45-55 DTCA, local less well developed foliation @ 30 DTCA; moderate silicification and 1% disseminated Py in (227.0-228.0); trace to 0.2% disseminated Py in other parts of interval, often as &lt;1 mm sized cubes; gradational upper and lower contacts</p>	223.00	224.00	P002823	1.00	0.197		0.197
			224.00	225.00	D925573	1.00	0.085		0.085
			225.00	226.00	P002824	1.00	0.014		0.014
225.80	229.35	<p>Sil60; Car40; Chl50; Epi35</p> <p><b>Silicification 60; Carbonatisation 40; Chloritisation 50; Epidotisation 35</b></p> <p>Strong alteration</p>	226.00	227.00	P002825	1.00	0.338		0.338
			227.00	228.00	P002827	1.00	0.870		0.870
			228.00	229.00	P002828	1.00	0.220		0.220
			229.00	230.00	P002829	1.00	0.058		0.058
		HP, 5/09/10: No Epidotization	230.00	231.00	D925574	1.00	0.076		0.076
			231.00	232.50	D925575	1.50	0.018		0.018
			232.50	234.00	D925576	1.50	<0.005		0.001
			234.00	235.50	D925577	1.50	<0.005		0.001
			235.50	237.00	D925578	1.50	<0.005		0.001
			237.00	238.70	D925580	1.70	0.013		0.013
			238.70	240.30	D925581	1.60	0.005		0.005
			240.30	241.90	D925582	1.60	0.006		0.006
			241.90	243.00	P002830	1.10	0.021		0.021
			243.00	244.20	D925583	1.20	<0.005		0.001
			244.20	245.40	D925584	1.20	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
245.30	251.20	Epi60; Chl50; Pot10; Ser <b>Epidotisation 60; Chloritisation 50; Potassic alteration 10; Sericitisation</b> Strong alteration  HP, 5/09/10: No epidotization; one 5 cm wide shear band at 246 m @ 60 DTCA; one shear band in (250.85-251.25) with foliation and fairly sharp upper contact @ 30 DTCA, fairly sharp lower contact @ 40 DTCA; rest of interval has several roughly parallel Chl-coated fractures and Qtz / Cb veinlets - up to 1 cm wide veins @ 45-55 DTCA; interval also contains five 5 - 35 cm wide Qtz, lesser Cc / Cb / Chl veins generally @ 50-60 DTCA, may contain trace disseminated Py; wall rock contains trace to 0.2%, locally 5% over a few cm, disseminated Py, often as <2 mm sized cubes	245.40	246.90	D925585	1.50	0.088		0.088
			246.90	248.00	D925586	1.10	0.020		0.020
			248.00	249.00	P002831	1.00	0.009		0.009
			249.00	250.40	D925587	1.40	0.051		0.051
			250.40	252.10	D925588	1.70	0.090		0.090
251.70	252.10	VEI;1;Cb Qz Cl;T;5°;Py00; <b>Vein 1 Carbonate Quartz Chlorite Tension 5° Pyrite 0.01%</b> HP, 5/09/10: 1 cm wide Cb-Chl-Qtz vein @ 5 DTCA; trace disseminated Py; trace to 0.5% disseminated Py and Py stringers in wall rock and earlier Qtz veinlets	252.10	253.60	D925590	1.50	0.022		0.022
			253.60	255.00	D925591	1.40	0.056		0.056
			255.00	256.50	D925592	1.50	<0.005		0.001
			256.50	258.00	D925593	1.50	<0.005		0.001
			258.00	259.50	D925594	1.50	<0.005		0.001
			259.50	261.00	D925596	1.50	0.006		0.006
			261.00	262.50	D925597	1.50	0.081		0.081
264.00	291.00	FRC; FOL; CNR <b>Fractured ; Foliation; Core Not recovered</b> Intense fracturation Core not recovered from 284.5m to 285m Fracture 10 TCA from 289.3 to 289.7  HP, 5/09/10: Fracture zone starts at 264.0 m (change from 272.0 m); Chl-coated fractures; (276.0-291.0) non-foliated but with roughly parallel alignment of most Qtz / Cb hairline fractures - veinlets @ 35-60 DTCA, this interval also includes ten scattered 2-8 cm wide Qtz-Cc-Cb-Chl veins @ 45-80 DTCA, veins may contain trace <2 mm sized Py cubes, adjacent wall rock may also contain up to 1% <2 mm sized disseminated Py cubes over a few cm	264.00	265.50	D925600	1.50	0.007		0.007
			265.50	267.00	D925601	1.50	<0.005		0.001
266.50	271.00	Chl70 <b>Chloritisation 70</b>	267.00	268.00	P002833	1.00	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description		Analyse							
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
270.80	272.00	chl alt.	268.00	269.50	D925602	1.50	0.029		0.029
			269.50	271.00	D925603	1.50	0.012		0.012
		HP, 5/09/10: Chl-coated fractures; wall rock is hematized I2D; BX	271.00	272.00	P002834	1.00	0.007		0.007
		<b>Syenite; Breccia</b> Breccia. Red dark green. Highly fractured. Strong chlorite alteration. Matrix silica. Phenos are 5-7 mm cemented in chlorite. No mineralization. Gradational contact.	272.00	273.00	P002835	1.00	1.660		1.660
272.30	276.00	HP, 5/09/10: Interval change from (270.0-272.0) to (270.8-272.0); crackle breccia to clast supported breccia; Chl-rich matrix; 0.2% disseminated Py in matrix; gradational contacts; breccia occurs in (264.0-291.0) fracture zone; (271.85-272.0) badly broken core, fault breccia, Chl-rich matrix, some up to 2 cm wide Qtz veins	273.00	274.00	P002836	1.00	1.635		1.635
		<b>Silicification 40; Chloritisation 40</b>	274.00	275.00	P002837	1.00	1.140		1.140
		Sili alt.	275.00	276.00	P002838	1.00	0.353		0.353
			276.00	277.00	P002839	1.00	0.018		0.018
		HP, 5/09/10: Silicification in (272.3-276.0), (change from 271.0-295.0); also abundant Chl-coated fractures; 2-5% fine disseminated Py, local Py stringers as well	277.00	278.50	D925604	1.50	<0.005		0.001
			278.50	280.00	D925605	1.50	<0.005		0.001
			280.00	281.50	D925606	1.50	0.011		0.011
			281.50	283.00	D925607	1.50	<0.005		0.001
			283.00	284.50	D925608	1.50	0.009		0.009
			285.00	286.50	D925610	1.50	0.006		0.006
			286.50	288.00	D925611	1.50	0.016		0.016
			288.00	289.50	D925612	1.50	0.006		0.006
			289.50	291.00	D925613	1.50	<0.005		0.001
			291.00	292.00	P002840	1.00	<0.005		0.001
			292.00	293.70	D925614	1.70	<0.005		0.001
			293.70	295.40	D925615	1.70	<0.005		0.001
			295.40	297.00	D925616	1.60	<0.005		0.001
	297.00	298.50	D925617	1.50	<0.005		0.001		
	298.50	300.00	D925618	1.50	0.005		0.005		
	300.00	301.50	D925620	1.50	<0.005		0.001		
	301.50	303.00	D925621	1.50	<0.005		0.001		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
303.00	367.65	Pot60; Sil50 <b>Potassic alteration 60; Silicification 50</b> Potassic and silice alt	303.00	304.00	P002841	1.00	0.033		0.033
			304.00	305.00	P002842	1.00	0.053		0.053
			305.00	306.00	P002843	1.00	0.208		0.208
306.00	311.00	Py02 <b>Pyrite 2%</b> HP, 6/09/10: Highly fractured Syenite; Chl-coated fractures; moderately chloritized wall rock; local cm-dm scale fractured silicified intervals with 2-5% fine disseminated Py and Py in stringers	306.00	307.00	P002844	1.00	0.310		0.310
			307.00	308.00	P002845	1.00	0.451		0.451
			308.00	309.00	P002846	1.00	0.423		0.423
			309.00	310.00	P002847	1.00	0.576		0.576
			310.00	311.00	P002848	1.00	0.122		0.122
			311.00	312.00	P002850	1.00	0.050		0.050
			312.00	313.50	D925622	1.50	<0.005		0.001
			313.50	315.00	D925623	1.50	0.021		0.021
314.10	350.90	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Dark green with pinkish-white. Medium grains. Massive. Gabroic texture. 20% euhedrals Fld (3-4 mm) weakly albitised and weak potassic alteration. Alterations : Weak CL, weak potassic, weak ALB and weak SI Micro-fractures filled with silica-carbonate fluids and magnetite. 10-20% disseminated magnetite. Mag+++ . No mineralization. Upper gradational contact and lower shap contact at 351.9m, 40 TCA.  HP, 6/09/10: Not a Gabbro, just a less hematitized Syenite (almost a "fresh" Syenite); chloritized; 5-10% relatively unaltered to, locally, completely chloritized mm-sized Fspar phenocrysts; fractured - irregular Chl-coated fractures, local dm scale brecciated intervals; scattered late through-going Chl-coated fractures	315.00	316.50	D925624	1.50	<0.005		0.001
			316.50	318.00	D925625	1.50	<0.005		0.001
			318.00	319.50	D925626	1.50	<0.005		0.001
			319.50	321.00	D925627	1.50	<0.005		0.001
			321.00	322.50	D925628	1.50	<0.005		0.001
			322.50	324.00	D925630	1.50	<0.005		0.001
			324.00	325.50	D925631	1.50	0.011		0.011
			325.50	327.00	D925632	1.50	<0.005		0.001
			327.00	328.50	D925633	1.50	<0.005		0.001
			328.50	330.00	D925634	1.50	<0.005		0.001
			330.00	331.50	D925636	1.50	<0.005		0.001
			331.50	333.00	D925637	1.50	<0.005		0.001
			333.00	334.50	D925638	1.50	<0.005		0.001
			334.50	336.00	D925640	1.50	<0.005		0.001
			336.00	337.50	D925641	1.50	<0.005		0.001
337.50	339.00	D925642	1.50	<0.005		0.001			
339.00	340.50	D925643	1.50	0.006		0.006			
340.00	340.10	VEI;10;Cc Qz Cl;T;60°;Py00.5; <b>Vein 10 Calcite Quartz Chlorite Tension 60° Pyrite 0.5%</b> HP, 6/09/10: 10 cm wide foliated - laminated Cc-Qtz-Chl vein @ 60 DTCA; up to 1% disseminated Py and Py along foliation - laminations	340.50	342.00	D925644	1.50	<0.005		0.001
			342.00	343.50	D925645	1.50	<0.005		0.001
			343.50	345.00	D925646	1.50	<0.005		0.001
			345.00	346.50	D925647	1.50	<0.005		0.001
			346.50	348.00	D925648	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
350.90	392.00	<p>SY POR</p> <p><b>Syenite Porphyry Intrusive</b></p> <p>Dark green to green-pink. Plagio and Fld medium grained.</p> <p>Alteration : Medium CL, medium potassic, weak pervasive HEM.</p> <p>Tr to no disseminated pyrite. Upper contact at 351.9m, 40 TCA.</p> <p>Foliation 50 TCA. Several micro-fractures filled with silica-carbonate fluids. Stringers of magnetite disseminated. Mag+++</p> <p>HP, 6/09/10: Not a Diorite - Gabbro, just a Syenite; only about 1% scattered mm-sized Fspar phenocrysts; chloritized; weakly hematitized; scattered Chl-coated fractures</p>	348.00	349.50	D925650	1.50	<0.005		0.001
			349.50	351.00	D925651	1.50	<0.005		0.001
			351.00	352.50	D925652	1.50	<0.005		0.001
			352.50	354.00	D925653	1.50	0.010		0.010
353.20	353.45	<p>FOL; CIS</p> <p><b>Foliation 35°; Sheared</b></p> <p>HP, 6/09/10: Shear zone; moderately developed foliation @ 35 DTCA (parallel alignment of Sericite flakes); trace disseminated Py; gradational upper contact, sharp lower contact marked by a 1 cm wide Cc vein @ 45 DTCA with it's upper margin coated with a thin layer of flakey-powdery Chl</p>	354.00	355.50	D925654	1.50	<0.005		0.001
			355.50	357.00	D925655	1.50	<0.005		0.001
			357.00	358.50	D925656	1.50	<0.005		0.001
			358.50	360.00	D925657	1.50	0.060		0.060
			360.00	361.50	D925658	1.50	<0.005		0.001
			361.50	363.00	D925660	1.50	<0.005		0.001
363.00	363.55	<p>STW;20%;Qz Cb Cc;T;;Py00;</p> <p><b>Stockwerk 20% Quartz Carbonate Calcite Tension Pyrite 0.01%</b></p> <p>HP, 6/09/10: Irregular 0.5-1.5 cm wide Qtz, minor Cb, veins that curve from 35 to 0 DTCA, also occur @ 50-85 DTCA, may be offset by fractures; trace disseminated Py; two Cc veins @ 25 DTCA; well developed Chl-Ser alteration halo around these veins, upper contact at core break, sharp but irregular lower contact @ 55 DTCA</p>	363.00	364.50	D925661	1.50	<0.005		0.001
			364.50	366.00	D925662	1.50	<0.005		0.001
			366.00	367.60	D925663	1.60	<0.005		0.001
			367.60	369.30	D925664	1.70	<0.005		0.001
367.65	372.60	<p>Epi60; Chl40; Sil30</p> <p><b>Epidotisation 60; Chloritisation 40; Silicification 30</b></p> <p>Strong alterations</p> <p>HP, 6/09/10: No Epidotization; chloritization, lesser sericitization, carbonatization; trace disseminated Py</p>	369.30	370.30	D925665	1.00	0.032		0.032
367.65	367.90	<p>FOL; CIS</p> <p><b>Foliation 70°; Sheared</b></p> <p>HP, 6/09/10: Shear - vein zone; 50% well foliated Ser-Chl-rich Syenite intercalated with 50% 3-4 cm wide Qtz, minor Cb, veins roughly @ 70 DTCA; trace disseminated Py; fairly regular</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
369.35	370.20	slightly diffuse upper contact @ 45 DTCA, fairly regular slightly diffuse lower contact @ 60 DTCA VEI;85;Qz Fp Cb Cl;T;55°;Py00.1; <b>Vein 85 Quartz Feldspath (alkaline) Carbonate Chlorite Tension 55° Pyrite 0.1%</b> HP, 6/09/10: Qtz-Fspar (orange)-Cb-Chl vein over 85 cm; sharp irregular contacts; foliated-sericitized-chloritized wall rock inclusions occurring as slivers at roughly 55 DTCA; 0.1% disseminated Py, mostly in wall rock slivers; 0.5-1% disseminated Py over ~10 cm in overlying and underlying wall rock	370.30	372.00	D925666	1.70	0.010		0.010
			372.00	373.50	D925667	1.50	0.032		0.032
372.60	377.55	Sil60; Pot30; Epi30; Chl40 <b>Silicification 60; Potassic alteration 30; Epidotisation 30; Chloritisation 40</b> Strong alterations  HP, 6/09/10: No Epidotization; chloritization, lesser sericitization, carbonatization	373.50	375.00	D925668	1.50	0.006		0.006
			375.00	376.50	D925670	1.50	0.025		0.025
			376.50	377.40	P002851	0.90	0.033		0.033
376.70	377.00	VEI;10;Qz Cc Cb Cl;T;60°;Py00; <b>Vein 10 Quartz Calcite Carbonate Chlorite Tension 60° Pyrite 0.01%</b> quartz vein  HP, 6/09/10: Qtz-Cc-Cb-Chl vein over 30 cm; trace disseminated Py	377.40	379.10	D925671	1.70	<0.005		0.001
			379.10	380.80	D925672	1.70	<0.005		0.001
			380.80	382.50	D925673	1.70	<0.005		0.001
			382.50	384.00	D925674	1.50	<0.005		0.001
			384.00	385.50	D925676	1.50	<0.005		0.001
			385.50	387.00	D925677	1.50	<0.005		0.001
			387.00	388.40	D925678	1.40	<0.005		0.001
			388.40	389.70	D925680	1.30	<0.005		0.001
389.90	390.60	VEI;70;Qz Cb Cc;T;15°;Py00.5; <b>Vein 70 Quartz Carbonate Calcite Tension 15° Pyrite 0.5%</b> HP, 6/09/10: Set of at least ten 0.5-2 cm wide Qtz, lesser Cb-Cc, veins @ 15 DTCA over 70 cm; veins are barren but intercalated foliated Syenite contains up to 2% disseminated Py as <2 mm sized cubes	389.70	390.70	D925681	1.00	0.060		0.060
			390.70	392.00	D925682	1.30	<0.005		0.001
392.00	423.00	SY; FRA; BR <b>Syenite; Fractured; Brecciated</b> Purple to purple-green-gray. Fld completely altered. Breccia with fractures. Matrix is silica and carbonate.	392.00	393.30	D925683	1.30	<0.005		0.001
			393.30	394.60	D925684	1.30	0.013		0.013
			394.60	396.00	D925685	1.40	0.159		0.159

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
<p>Alteration : medium Si, strong CL, weak ALB, medium CARB, weak pervasive HEM, medium Potassic.</p> <p>Strong epidote alteration from 404.6m to 406.6m. (HP, Sericitization, not Epidotization)</p> <p>Fine to medium grains. Lots of fractured (25%) filled with silicate-carbonate fluids. Micro-fractures filled with chlorite and Py.</p> <p>2-3% disseminated Py</p> <p>Gradational upper and lower contact. Disseminated magnetite (mag+++).</p> <p>HP, 7/09/10: Fractured - brecciated, not a breccia, although locally a breccia over up to 30 cm; fracture fill is Cc, minor Qtz / Cb</p>									
396.00	404.80	FOL	396.00	397.00	P002852	1.00	0.357		0.357
		<b>Foliation 40°</b>	397.00	398.00	P002853	1.00	0.491		0.491
		Foliation	398.00	399.00	P002854	1.00	0.006		0.006
			399.00	400.00	P002855	1.00	0.005		0.005
			400.00	401.00	P002856	1.00	0.010		0.010
			401.00	402.00	P002857	1.00	0.044		0.044
			402.00	403.00	P002858	1.00	0.005		0.005
			403.00	404.00	228779	1.00	0.011		0.011
			404.00	405.30	D925686	1.30	0.163		0.163
396.00	398.00	Py00.2							
		<b>Pyrite 0.2%</b>							
		HP, 7/09/10: Highly fractured Syenite; Chl-coated fractures; minor silicification; trace - 0.2% disseminated Py							
404.60	406.60	Epi70							
		<b>Epidotisation 70</b>							
		Strong epidotisation							
		HP, 7/09/10: Sericitization, not Epidotization							
404.80	406.60	FOL; CIS	405.30	406.70	D925687	1.40	0.058		0.058
		<b>Foliation 40°; Sheared</b>							
		HP, 7/09/10: Alteration - shear zone; strong sericitization in (404.8-406.6); moderately to well developed foliation @ 40 DTCA in (405.4-406.3) also with strong chloritization; upper contact marked by a 15 cm wide Cc, minor Qtz, vein with included up to 1 cm wide strongly carbonatized (Cc) wall rock slivers, all with ~0.3% very fine disseminated Py; most of							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
406.60	440.00	remainder of interval contains trace - 0.2% very fine disseminated Py and Py stringers, locally up to 1% Py over a few cm, rare up to 2 mm sized Py cubes as well; end of shear zone at 406.4 m and marked by parallel Cc veinlets @ 55 DTCA and 2% very fine-grained Py stringers over 10 cm FOL <b>Foliation 40°</b> Foliation	406.70	408.00	D925688	1.30	<0.005		0.001
			408.00	409.50	D925690	1.50	0.018		0.018
			409.50	411.00	D925691	1.50	<0.005		0.001
			411.00	412.00	D925692	1.00	0.113		0.113
412.00	413.00	Py03 <b>Pyrite 3%</b> HP, 7/09/10: Highly fractured Syenite; Chl-coated fractures; 15 cm long carbonatized (Cc) - silicified interval with 3% fine Py disseminations and mm long stringers	412.00	413.00	P002859	1.00	0.126		0.126
			413.00	414.00	D925693	1.00	<0.005		0.001
			414.00	415.50	D925694	1.50	0.031		0.031
			415.50	417.00	D925695	1.50	0.013		0.013
			417.00	418.50	D925696	1.50	0.016		0.016
			418.50	420.00	D925697	1.50	<0.005		0.001
			420.00	421.50	D925698	1.50	<0.005		0.001
			421.50	423.00	D925700	1.50	<0.005		0.001
423.00	430.50	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Dark purple to purple-pink. Plagio and Fld medium grained. Altration : Medium CL, medium potassic. Tr to no disseminated pyrite. Gradational upper and lower contact. Foliation 40-50 TCA. Several micro-fractures filled with silica-carbonate fluids. Few quartz veins. Magnetite disseminated. Mag+++  HP, 7/09/10: Not a Diorite, just a Syenite; relatively unaltered; chloritized mafic minerals; 5% mm sized Fspar phenocrysts; fine-medium-grained groundmass	423.00	424.50	D925701	1.50	<0.005		0.001
			424.50	426.00	D925702	1.50	<0.005		0.001
			426.00	427.50	D925703	1.50	<0.005		0.001
			427.50	429.00	D925704	1.50	<0.005		0.001
			429.00	430.50	D925705	1.50	<0.005		0.001
430.50	504.10	SY POR; POR; BR <b>Syenite Porphyry Intrusive; Porphyric; Brecciated</b> Purple to purple-pink-gray. Fld completely altered. Breccia with fractures. Matrix is silica and carbonate. Alteration : strong Si, strong CL, weak ALB, medium CARB, weak HEM, medium Potassic. Medium grains. Lots of fractured (25%) filled with sillcate-carbonate fluids. Micro-fractures filled with chlorite and Py. 2-3% disseminated Py and patches in breccia.	430.50	432.00	P002914	1.50	0.017		0.017
			432.00	433.50	P002915	1.50	0.043		0.043
			433.50	435.00	P002916	1.50	0.024		0.024
			435.00	436.50	P002917	1.50	0.015		0.015
			436.50	438.00	P002918	1.50	0.043		0.043
			438.00	439.00	P002919	1.00	<0.005		0.001
			439.00	440.00	P002920	1.00	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
440.70	444.40	I2D; BR <b>Syenite; Brecciated</b> Breccia. Light gray-pink. Highly fractured. Medium chlorite alteration, strong silicification and weak hematisation. Matrix silica and carbonate. 2-3% Py. Gradational contact.  HP, 7/09/10: Not an Intermediate Volcanic (Flow); brecciated Syenite; pervasive carbonatization (Cc) and Cc flooding; some Qtz-Cb veining as well; silicified; sericitized; highly fractured; 2-3% fine disseminated Py, locally up to 5% Py	440.00	441.00	P002860	1.00	1.055	3.16	1.055
			441.00	442.00	P002861	1.00	3.140		3.160
			442.00	443.00	P002862	1.00	1.805		1.805
			443.00	444.00	P002863	1.00	0.928		0.928
			444.00	445.00	P002864	1.00	0.134		0.134
			445.00	446.00	P002865	1.00	0.366		0.366
			446.00	447.00	P002867	1.00	0.152		0.152
			447.00	448.00	P002868	1.00	0.006		0.006
			448.00	449.00	208743	1.00	0.008		0.008
			449.00	450.00	208744	1.00	0.007		0.007
			450.00	451.50	208745	1.50	0.007		0.007
			451.50	453.00	208746	1.50	0.008		0.008
			453.00	454.00	P002869	1.00	0.051		0.051
454.00	457.50	Py00.2 <b>Pyrite 0.2%</b> HP, 7/09/10: 0.1-0.2% very fine disseminated Py; locally up to 1-5% Py as disseminations and in stringers; highly fractured Syenite; pervasive carbonatization (Cb); scattered Qtz - Cc veinlets	454.00	455.00	P002870	1.00	1.440		1.440
			455.00	456.00	208756	1.00	0.217	0.217	
			456.00	457.50	208757	1.50	1.170	1.170	
			457.50	459.00	208758	1.50	0.029	0.029	
			459.00	460.50	208759	1.50	0.105	0.105	
			460.50	462.00	208761	1.50	0.089	0.089	
			462.00	463.50	208762	1.50	0.018	0.018	
			463.50	465.00	208763	1.50	<0.005	0.001	
			465.00	466.50	208764	1.50	0.042	0.042	
			466.50	468.00	208765	1.50	<0.005	0.001	
468.00	482.00	FOL <b>Foliation 70°</b> Fol70	468.00	469.50	208766	1.50	<0.005	0.001	
			469.50	471.00	208767	1.50	<0.005	0.001	
471.00	491.00	Chl40; Epi40; Sil20 <b>Chloritisation 40; Epidotisation 40; Silicification 20</b> Strong alteration	471.00	472.00	208768	1.00	<0.005	0.001	
			472.00	472.90	208769	0.90	<0.005	0.001	
472.90	474.00	Py03 <b>Pyrite 3%</b> HP, 7/09/10: One 10 cm wide pervasively carbonatized (Cc), minor silicification, band @ 40 DTCA; up to 3% fine disseminated Py	472.90	474.00	P002871	1.10	2.490	2.490	
			474.00	475.00	208771	1.00	<0.005	0.001	
			475.00	476.50	208772	1.50	<0.005	0.001	
			476.50	477.50	P002872	1.00	0.006	0.006	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
482.00	497.40	<p>FOL</p> <p><b>Foliation 40°</b></p> <p>HP, 7/09/10: Moderately developed foliation - alignment of Ser-Chl - coated fractures @ 40 DTCA; some foliation parallel Cc / Qtz veinlets, rare up to 2 cm wide veins; pervasively carbonatized (Cb) wall rock, (491.6-497.4) is also strongly sericitized</p>	477.50	478.50	208773	1.00	<0.005		0.001
			478.50	480.00	208774	1.50	<0.005		0.001
			480.00	481.00	208775	1.00	<0.005		0.001
			481.00	482.00	D925706	1.00	<0.005		0.001
			482.00	483.00	D925707	1.00	<0.005		0.001
			483.00	484.50	D925708	1.50	<0.005		0.001
			484.50	486.00	D925710	1.50	0.028		0.028
			486.00	487.50	D925711	1.50	0.023		0.023
			487.50	489.00	D925712	1.50	0.006		0.006
			489.00	490.50	D925713	1.50	<0.005		0.001
491.00	504.10	<p>Epi90</p> <p><b>Epidotisation 90</b></p> <p>Epid90</p>	490.50	492.00	D925714	1.50	<0.005		0.001
			492.00	493.50	D925716	1.50	<0.005		0.001
			493.50	494.90	D925717	1.40	<0.005		0.001
			494.90	496.20	D925718	1.30	<0.005		0.001
497.40	506.20	<p>FOL; O; CIS</p> <p><b>Foliation 25°; Lamination; Sheared</b></p> <p>HP, 7/09/10: Shear zone; well developed foliation and discontinuous parallel &lt;5 mm wide laminations @ 25 DTCA; strongly sericitized - carbonatized (Cb) - chloritized; rare disseminated Py, up to 0.2% locally over a few cm; sharp upper contact @ 25 DTCA, truncates overlying foliation @ 15-20 DTCA; sharp irregular lower contact @ 15 DTCA; (502.2-506.2) is the transition zone between the overlying shear zone and the underlying silicified breccia zone</p>	496.20	497.40	D925720	1.20	<0.005		0.001
			497.40	498.60	D925721	1.20	<0.005		0.001
			498.60	499.80	D925722	1.20	<0.005		0.001
			499.80	501.00	D925723	1.20	<0.005		0.001
			501.00	502.40	208776	1.40	0.028		0.028
			502.40	504.00	208777	1.60	0.030		0.030
504.10	539.70	<p>BSF</p> <p><b>Breccia silicified zone</b></p> <p>Breccia. Gray. Intense silicification (HP, Cc carbonatization &gt;&gt; silicification), strong pervasive epidotisation (HP, No, sericitization) and medium carbonatization, medium albitisation and fuchsite. Few phenos. Intense fractures (60%). Matrix silica and carbonate. Micro-fractures filled with chlorite. 3-5% stringers and disseminated Py. Upper contact 30 TCA.</p> <p>HP, 7/09/10: No epidotization, this is sericitization; interval contains dm scale remnants of foliated - sheared Ser-Cb - rich syenite with foliation @ 0-20 DTCA; pervasive Cc carbonatization with lesser silicification;</p>	504.00	505.00	P002873	1.00	0.407		0.407

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
504.10	539.70	most intense Cc carbonatization - silicification in (504.1-515.0), (515.0-539.7) is foliated - sheared Syenite with 10-50%, locally 90%, Cc carbonatization - silicification; sharp slightly irregular lower contact for the interval @ 30 DTCA Sil80; Epi40; FCT15 <b>Silicification 80; Epidotisation 40; Fuchsitization 15</b> strong alterations							
504.10	539.70	Py04 <b>Pyrite 04%</b> Intense silicification, strong pervasive epidotisation and medium carbonatation, medium albitisation and fuschite. Few phenos. Intense fractures (60%). Matrix silica and carbonate. Micro-fractures filled with chlorite. 3-5% stringers and disseminated Py.	505.00	506.00	P002874	1.00	2.780		2.780
			506.00	507.00	P002875	1.00	3.330	3.57	3.570
			507.00	508.00	P002876	1.00	3.350	3.72	3.720
			508.00	509.00	P002877	1.00	4.230	4.70	4.700
			509.00	510.00	P002878	1.00	2.460		2.460
			510.00	511.00	P002879	1.00	1.405		1.405
			511.00	512.00	P002880	1.00	0.697		0.697
			512.00	513.00	P002881	1.00	1.275		1.275
			513.00	514.00	P002882	1.00	1.640		1.640
			514.00	515.00	P002883	1.00	2.740		2.740
			515.00	516.00	P002884	1.00	1.050		1.050
			516.00	517.00	P002885	1.00	1.555		1.555
			517.00	518.00	P002886	1.00	1.265		1.265
			518.00	519.00	P002887	1.00	2.170		2.170
			519.00	520.00	P002888	1.00	0.912		0.912
			520.00	521.00	P002890	1.00	1.910		1.910
			521.00	522.00	P002891	1.00	0.822		0.822
			522.00	523.00	P002892	1.00	1.040		1.040
			523.00	524.00	P002893	1.00	1.850		1.850
			524.00	525.00	P002894	1.00	0.773		0.773
			525.00	526.00	P002895	1.00	1.495		1.495
			526.00	527.00	P002896	1.00	1.360		1.360
			527.00	528.00	P002897	1.00	2.020		2.020
			528.00	529.00	P002898	1.00	0.435		0.435
			529.00	530.00	P002899	1.00	1.370		1.370
			530.00	531.00	P002900	1.00	2.990		2.990
			531.00	532.00	P002901	1.00	2.730		2.730
			532.00	533.00	P002902	1.00	2.810		2.810

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
539.70	557.10	TZ; I2D; B  <b>Transitional Zone; Syenite; Breccia</b> Transitional syenite zone. Purple-green to purple-pink-yellow. Fls Phenos almost all disappeared and strongly CL altered. Fine to medium grains. Micro-fractures filled with silica-carbonate fluids and chlorite. Alterations: strong EPI (HP, Sericite, not Epidote), weak SI, medium CARB, medium CL. Trace to no Py. Trace of Arsenopyrite. Mag++. Gradational upper and lower contacts.	533.00	534.00	228772	1.00	0.738		0.738
			534.00	535.00	228773	1.00	1.040		1.040
			535.00	536.00	228774	1.00	1.705		1.705
			536.00	537.00	228775	1.00	2.220		2.220
			537.00	538.00	228776	1.00	1.260		1.260
			538.00	539.00	228777	1.00	1.875		1.875
			539.00	540.00	228778	1.00	0.775		0.775
			540.00	541.50	208778	1.50	0.009		0.009
			541.50	543.00	208779	1.50	0.018		0.018
			543.00	544.50	208781	1.50	0.181		0.181
539.70	554.80	FOL; O  <b>Foliation 25°; Lamination</b> HP, 8/09/10: Foliation - mm-spaced discontinuous <3 mm wide Ser-Chl laminations (fracture coatings) @ 20-30 DTCA	544.50	546.00	208782	1.50	<0.005		0.001
			546.00	547.50	208783	1.50	0.023		0.023
			547.50	549.00	208784	1.50	<0.005		0.001
			549.00	550.40	208785	1.40	<0.005		0.001
			550.40	552.00	D925724	1.60	<0.005		0.001
			552.00	553.10	D925725	1.10	<0.005		0.001
			553.10	554.10	D925726	1.00	0.007		0.007
549.40	557.10	Ser; Car  <b>Sericitisation; Carbonatisation</b> ep70  HP, 8/09/10: Sericitization and Cb carbonatization	554.10	555.00	228781	0.90	0.037		0.037
			554.80	554.90	FRC  <b>Fractured</b> core fractured and broken	555.00	556.00	228782	1.00
554.90	556.00	FOL; CIS  <b>Foliation 25°; Sheared</b> HP, 8/09/10: Shear zone; moderately well developed foliation @ 25 DTCA; includes foliation parallel elongated completely Chloritized Fspar phenocrysts; upper contact in broken core, lower contact marked by a 12 cm wide barren massive Qtz vein; foliated rock includes scattered up to 4 mm long cross cutting Aspy grains and trace disseminated Py	555.00	556.00	228782	1.00	0.013		0.013
			555.80	555.84	VEI; Qz; T; 80°;  <b>Vein Quartz Tension 80°</b> vein Qtz	556.00	557.00	228783	1.00

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
556.08	556.20	VEI;;Qz;T;60°; <b>Vein Quartz Tension 60°</b> qtz vein	557.00	558.00	228785	1.00	0.012		0.012
557.10	600.90	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Dark-purple to pink-purple. 40% euhedrals Fld phénos (3-8mm) and 5% lath phenos (3mmX5mm). 75% phenos from 572m to 579m. Fld alteration : weak chlorite and weak albite. Pervasive strong EP (HP, Sericite, not Epidote) and CL alteration. Groundmass alteration : Pervasive strong EP (HP, Sericite, not Epidote) and CL alteration. Fractures filled with carbonate. Traces of Py. Disseminated magnetite. Mag++++	558.00	559.00	228786	1.00	<0.005		0.001
			559.00	560.00	D925727	1.00	0.011		0.011
559.10	559.90	VEI;1.5;Cb Qz Cc;T;; <b>Vein 1.5 Carbonate Quartz Calcite Tension</b> HP, 8/09/10: Up to 1.5 cm wide Cb-Qtz-Cc vein @ 10 DTCA, barren; at least seven other Qtz-Cb-Cc veinlets - up to 2 cm wide veins (discontinuous) @ 2-30 DTCA, barren; wall rock contains trace, locally up to 0.5%, disseminated Py	560.00	561.70	D925728	1.70	0.014		0.014
			561.70	563.40	D925730	1.70	<0.005		0.001
563.40	566.50	FRC <b>Fractured</b> HP, 8/09/10: Moderately to highly fractured; Qtz / Chl filled fractures, veinlets; locally up to 3% disseminated Py over a few cm; mostly cubic Py, up to 3 mm in size	563.40	564.50	P002903	1.10	0.005		0.005
			564.50	565.50	P002904	1.00	0.008		0.008
			565.50	566.50	P002905	1.00	0.005		0.005
			566.50	568.20	D925731	1.70	<0.005		0.001
			568.20	569.90	D925732	1.70	<0.005		0.001
			569.90	571.50	D925733	1.60	<0.005		0.001
			571.50	573.00	D925734	1.50	<0.005		0.001
			573.00	574.50	D925735	1.50	<0.005		0.001
			574.50	576.00	D925736	1.50	<0.005		0.001
			576.00	577.50	D925737	1.50	<0.005		0.001
			577.50	579.00	D925738	1.50	<0.005		0.001
			579.00	580.50	D925740	1.50	<0.005		0.001
			580.50	582.20	D925741	1.70	<0.005		0.001
			582.20	583.90	D925742	1.70	<0.005		0.001
583.90	585.00	D925743	1.10	0.020		0.020			
584.00	593.00	FOL; CIS; O; FRC <b>Foliation 30°; Sheared; Lamination; Fractured</b> HP, 8/09/10: Shear zone; mostly with moderately well developed	585.00	585.80	P002906	0.80	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		foliation and foliation parallel mm wide laminations @ 30 DTCA; foliation curves from 10 to 0 DTCA downhole in lower 1 m of interval; mostly strongly Chloritized, also carbonatized (Cb) and sericitized; locally highly fractured - brecciated - silicified; 10% overall, locally 50%, silicification - Qtz flooding and mostly foliation parallel Qtz, minor Cb or Cc, veining (up to 4 cm wide veins); rare disseminated Py, often as up to 1 mm sized cubes, or Py stringers; local remnants of Syenite Lath Porphyry (10-20% Fspar laths); irregular gradational upper contact; gradational lower contact, foliated rock grades into brecciated Syenite; 5% Aspy-Py disseminations and mm sized aggregates in lower 5 cm of interval						
585.20	593.40	BSF	585.80	586.80	D925744	1.00	<0.005	0.001
		<b>Breccia silicified zone</b>	586.80	588.00	D925745	1.20	<0.005	0.001
		Breccia. Dark-Gray-Green-Black. Strong silicification, strong epidotisation. Few phenos. Intense fractures (40%). Matrix silica and carbonate. Micro-fractures filled with chlorite and epidote.	588.00	589.50	D925746	1.50	0.022	0.022
		1% disseminated Py. Shear zone. Foliation 30TCA .Upper contact 40 TCA and lower contact 80 TCA. Weak mag.	589.50	591.00	D925747	1.50	0.011	0.011
			591.00	592.00	D925748	1.00	0.007	0.007
			592.00	593.00	D925750	1.00	0.012	0.012
			593.00	594.00	P002907	1.00	0.017	0.017
593.55	595.15	I2D LT POR; LATH	594.00	595.50	D925751	1.50	0.125	0.125
		<b>Syenite Lath Porphyry Intrusive; Elongated phenocrysts</b>	595.50	597.00	D925752	1.50	0.005	0.005
		HP, 8/09/10: Syenite lath porphyry; 10-15% up to 2.5 cm long Fspar laths; most laths oriented @ 80-90 DTCA; moderately - highly fractured; chloritized, carbonatized (Cb), sericitized; 0.2% disseminated up to 3 mm sized euhedral grains of Py and Aspy; sharp irregular upper contact marked by a 0.5-1 cm wide Cc veinlet @ 90 DTCA, sharp but very irregular lower contact	597.00	598.30	D925753	1.30	<0.005	0.001
			598.30	599.65	D925754	1.35	0.008	0.008
			599.65	600.45	D925755	0.80	1.200	1.200
599.95	600.15	Py05						
		<b>Pyrite 5%</b>						
		HP, 8/09/10: 5-10% very fine disseminated Py, Py stringers, Py laminations; Py occurs in a Cc-rich vein-like structure; sharp upper contact @ 55 DTCA, sharp lower contact @ 30 DTCA						
600.00	601.90	B	600.45	601.70	D925757	1.25	0.009	0.009
		<b>Breccia</b>						
		Breccia. Dark-Gray-Green-Black. Strong silicification, strong epidotisation. Few phenos. Intense fractures (40%). Matrix silica and carbonate. Micro-fractures filled with chlorite and magnetite. Tr of Py. Upper contact 80 TCA and lower contact 70.						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
600.90	621.00	<p>Mag++++.</p> <p>SY POR; FOL; FRA; BR</p> <p><b>Syenite Porphyry Intrusive 25°; Foliation ; Fractured; Brecciated</b></p> <p>(Dark green to black. Aphanitic, massive. Vuggy section from 609.8m to 611m (HP, interval is (609.95-611.2); fairly sharp upper contact @ 25 DTCA, sharp lower contact @ 15 DTCA; strongly silicified (albitized?); up to 3% disseminated Py, Py stringers). Strong ALB alteration, medium CL, medium potassic and weak SI. Bleached from 613 (HP, 614) m to 621 m with few stringers of chlorite. Arseno at 615.55m. Strong foliation 20 TCA.</p> <p>Micro-fractures filled with magnetite. 2 silica veins (at 604.6m) with patch of CPO. Tr. of Py. (HP, 8/09/10; originally logged as Mafic Metavolcains in (609.3-621.0))</p> <p>HP, 8/09/10: (600.9-614.0) Syenite; 5% fspar phenocrysts; dark green, strongly chloritized; fractured - brecciated; dm scale intervals with foliation @ 20-30 DTCA (614.0-621.0) Syenite; pale- medium green; strongly sericitized; well foliated - sheared in lower 3 m of interval, foliation @ 20 DTCA (609.6-609.95) Silicified (albitized?); minor Cc carbonatization; 5-10% fine disseminated Py, Py stringers</p> <p>E.O.H. : 621m</p>	601.70	603.00	D925758	1.30	0.007		0.007
601.90	609.30	<p>V3; APH; MAS; MAG</p> <p><b>Mafic Meta-Volcanic ; Aphanitic; Massive rock; Magnetic</b></p> <p>Dark green to black. Aphanitic, massive. Vuggy section from 609.8m to 611m. Strong ALB alteration, medium CL, medium potassic and weak SI.</p> <p>Micro-fractures filled with magnetite. 2 silica veins (at 604.6m) with patch of CPO. Tr. of Py.</p>	603.00	604.00	D925760	1.00	<0.005		0.001
			604.00	605.00	P002908	1.00	0.009		0.009
			605.00	606.00	208786	1.00	0.006		0.006
			606.00	607.00	D925761	1.00	0.684		0.684
			607.00	608.10	208788	1.10	1.010		1.010
			608.10	609.00	P002909	0.90	0.167		0.167
			609.00	610.20	P002910	1.20	5.210	5.02	5.020
			610.20	611.10	P002911	0.90	3.660	3.95	3.950
			611.10	612.50	P002921	1.40	0.264		0.264
			612.50	614.00	P002922	1.50	<0.005		0.001
613.70	614.50	<p>FRC</p> <p><b>Fractured 40°</b></p> <p>fracture and broken core</p>	614.00	615.00	P002923	1.00	0.015		0.015
			615.00	616.00	P002912	1.00	0.208		0.208
			616.00	617.00	208789	1.00	0.051		0.051

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	617.00	618.00	208791	1.00	<0.005		0.001
	618.00	619.50	208792	1.50	<0.005		0.001
	619.50	621.00	208793	1.50	0.015		0.015
<p>621.00      Fin du sondage                  Nombre d'échantillons : 486                  Nombre d'échantillons QAQC : 55                  Longueur totale échantillonnée : 616.90</p>							



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.70	9.40	D925469	D925468	1.70	0.008	0.008
16.00	16.00	D925475	m	0.00	<0.005	0.001
24.40	24.40	D925479	O54Pa	0.00	2.800	2.800
46.00	46.00	P002768	O52Pb	0.00	0.304	0.304
52.00	53.00	208730	m	1.00	0.007	0.007
64.00	64.00	P002783	O53Pb	0.00	0.578	0.578
67.50	69.00	D925489	D925488	1.50	<0.005	0.001
100.50	100.50	D925499	O52Pb	0.00	0.309	0.309
111.50	113.00	208750	m	1.50	0.006	0.006
122.30	123.80	D925509	D925508	1.50	<0.005	0.001
130.40	130.40	D925515	m	0.00	<0.005	0.001
134.00	134.00	P002809	O54Pa	0.00	2.830	2.830
135.00	135.00	D925519	O53Pb	0.00	0.629	0.629
148.50	150.00	D925529	D925528	1.50	<0.005	0.001
161.70	161.70	D925539	O54Pa	0.00	2.820	2.820
183.00	184.50	D925549	D925548	1.50	0.369	0.369
190.60	190.60	D925555	m	0.00	<0.005	0.001
195.00	195.00	D925559	O52Pb	0.00	0.314	0.314
209.70	210.70	D925569	D925568	1.00	0.031	0.031
219.00	220.50	208740	O53Pb	1.50	0.644	0.644
226.00	226.00	P002826	O53Pb	0.00	0.619	0.619
235.50	235.50	D925579	O53Pb	0.00	0.614	0.614
250.40	252.10	D925589	D925588	1.70	0.056	0.056
258.00	258.00	D925595	m	0.00	<0.005	0.001
262.50	262.50	D925599	O54Pa	0.00	2.600	2.600
283.00	284.50	D925609	D925608	1.50	<0.005	0.001
298.50	298.50	D925619	O52Pb	0.00	0.338	0.338
310.00	310.00	P002849	O52Pb	0.00	0.322	0.322
321.00	322.50	D925629	D925628	1.50	<0.005	0.001
328.50	328.50	D925635	m	0.00	<0.005	0.001
333.00	333.00	D925639	O53Pb	0.00	0.630	0.630
346.50	348.00	D925649	D925648	1.50	<0.005	0.001
360.00	360.00	D925659	O54Pa	0.00	2.830	2.830

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
373.50	375.00	D925669	D925668	1.50	0.012	0.012
382.50	382.50	D925675	m	0.00	<0.005	0.001
387.00	387.00	D925679	O52Pb	0.00	0.315	0.315
403.00	404.00	228780	228779	1.00	0.006	0.006
406.70	408.00	D925689	D925688	1.30	<0.005	0.001
420.00	420.00	D925699	O53Pb	0.00	0.570	0.570
445.00	445.00	P002866	O54Pa	0.00	2.910	2.910
459.00	460.50	208760	O53Pb	1.50	1.010	1.010
472.00	473.00	208770	m	1.00	<0.005	0.001
483.00	484.50	D925709	D925708	1.50	<0.005	0.001
490.50	490.50	D925715	m	0.00	<0.005	0.001
494.90	494.90	D925719	O54Pa	0.00	2.780	2.780
519.00	519.00	P002889	O52Pb	0.00	0.328	0.328
541.50	543.00	208780	O53Pb	1.50	0.605	0.605
556.00	556.00	228784	O53Pb	0.00	0.617	0.617
560.00	561.70	D925729	D925728	1.70	<0.005	0.001
577.50	577.50	D925739	O52Pb	0.00	0.306	0.306
591.00	592.00	D925749	D925748	1.00	0.007	0.007
599.65	599.65	D925756	m	0.00	<0.005	0.001
601.70	601.70	D925759	O53Pb	0.00	0.633	0.633
615.00	615.00	P002913	O54Pa	0.00	2.860	2.860
616.00	617.00	208790	m	1.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-51

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie mine

Foré par : Foramex

Lot :

Décrit par : Genevieve Carignan

Du : 2009-05-05

Date de description : 2009-05-14

Au : 2009-05-08

Collet

Azimut : 157.91°  
 Plongée : -54.20°  
 Longueur : 221.50 m

UTM

Est	631 337.4
Nord	5 374 289.2
Élévation	301.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	158.00°	-53.30°	Non
Reflex	60.00	157.75°	-52.50°	Non
Reflex	90.00	159.05°	-52.30°	Non
Reflex	120.00	160.35°	-52.00°	Non
Reflex	150.00	160.45°	-51.80°	Non
Reflex	180.00	160.35°	-51.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

NAD 83, UTM Zone 17

Resampled by Carl Corriveau, avril 2010.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	6.00	MT <b>Casing</b> Casing							
6.00	13.30	BA <b>Mafic Meta-Volcanic</b> Volcanic rock. Dark green to pale green-yellowish aphanitic to fine grained matrix. Foliated @ 40° TCA and non magnetic.  Light weathering in the fractures. Light pervasive chloritisation and light pervasive epidotisation.  Tr-1% fine disseminated pyrite.	6.00	7.50	227229	1.50	0.055		0.055
			7.50	9.00	227231	1.50	0.051		0.051
			9.00	10.50	227232	1.50	0.010		0.010
			10.50	12.00	227233	1.50	0.007		0.007
11.00	13.30	Blch <b>Bleaching</b> Light to moderate bleaching (epidote and quartz).	12.00	13.50	227234	1.50	0.018		0.018
13.30	194.10	SY POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Pale purple -greenish (71-93m grey-greenish) aphanitic to loc fine grained matrix with 3-5% Fp phenos (0.2-2cm). Local zones where Fp phenos are lath but there is no more phenos than the rest of the unit. Massive and non magnetic and heterogenous in the alteration.  1-2% Qz± Cc veins @ 60° TCA and 25° TCA.  Loc light chloritisation and light spotty sericitisation. Light weathering in the fractures until 90m. Loc light silicification and hematisation in veins and pervasive.  Tr-1% very fine to fine disseminated pyrite and traces of chalcopyrite.  Upper contact sharp @ 50° TCA.	13.50	15.00	227235	1.50	0.085		0.085
			15.00	16.50	227236	1.50	0.075		0.075
			16.50	18.00	227237	1.50	0.019		0.019
			18.00	19.50	227238	1.50	0.013		0.013
			19.50	21.00	227239	1.50	0.070		0.070
			21.00	22.50	227241	1.50	0.031		0.031
			22.50	24.00	227242	1.50	0.113		0.113
			24.00	25.50	227243	1.50	0.010		0.010
			25.50	27.00	227244	1.50	0.037		0.037
			27.00	28.50	227245	1.50	0.010		0.010
			28.50	30.00	227246	1.50	0.006		0.006
			30.00	31.00	P000074	1.00	0.021		0.021
			31.00	32.00	P000075	1.00	0.144		0.144
13.30	14.30	Epi <b>Epidotisation</b> Light pervasive apple green epidotisation.							
31.40	37.00	Sil <b>Silicification</b> Light to moderate pervasive silicification.							
31.40	37.00	Py03	32.00	33.00	P000076	1.00	2.570	3.57	3.570

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Pyrite 03%</b>	33.00	34.00	P000077	1.00	0.062		0.062
		2-4% very fine disseminated pyrite.	34.00	35.00	P000078	1.00	0.239		0.239
		Upper contact sharp but irregular.	35.00	36.00	P000079	1.00	0.080		0.080
			36.00	37.00	P000080	1.00	0.133		0.133
			37.00	38.00	P000081	1.00	0.008		0.008
			38.00	39.00	P000082	1.00	<0.005		0.001
			39.00	40.50	227247	1.50	0.009		0.009
			40.50	42.00	227248	1.50	0.140		0.140
			42.00	43.50	227249	1.50	0.176		0.176
			43.50	45.00	227251	1.50	0.041		0.041
44.50	48.60	STW;3%;Qz;;25°;;	45.00	46.00	227252	1.00	0.490		0.490
		<b>Stockwerk 3% Quartz 25°</b>	46.00	47.00	P000083	1.00	0.302		0.302
		2-4% Qz veins @ 20-30° TCA.							
46.50	56.20	Ser; Chl	47.00	48.00	P000084	1.00	0.454		0.454
		<b>Sericitisation; Chloritisation</b>							
		Light to moderate sericitisation and light chloritisation.							
47.30	48.65	I2D POR; POR	48.00	49.00	P000085	1.00	0.894		0.894
		<b>Syenite Porphyry Intrusive; Porphyric</b>	49.00	50.00	P000086	1.00	1.820		1.820
		5-7% Fp phenos (0.1-2cm).	50.00	51.00	P000087	1.00	1.735		1.735
			51.00	52.00	P000088	1.00	3.720	3.68	3.680
51.80	52.00	I2D LT POR	52.00	53.00	P000089	1.00	0.168		0.168
		<b>Syenite Lath Porphyry Intrusive</b>	53.00	54.00	P000090	1.00	1.105		1.105
		Intrusive rock. Purple-grey aphanitic matrix with 15-20% Lath Fp	54.00	55.00	P000091	1.00	1.765		1.765
		phenos aligned @ 50-60° TCA. Massive and non magnetic.	55.00	56.00	P000092	1.00	0.659		0.659
		Tr-1% white Qz veins @ 20° TCA.	56.00	57.00	P000093	1.00	6.080	5.84	5.840
		Tr very fine disseminated pyrite.							
		Sharp contact @ 50° TCA.							
56.20	59.40	Sil							
		<b>Silicification</b>							
		Moderate to high silicification. Smokey Qz.							
56.20	59.40	Py03	57.00	58.00	P000095	1.00	6.960	6.75	6.750
		<b>Pyrite 03%</b>	58.00	59.00	228830	1.00	2.030		2.030
		2-4% very fine disseminated pyrite.	59.00	60.00	228832	1.00	3.270	3.46	3.460

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			60.00	61.00	228833	1.00		0.130
			61.00	62.00	228834	1.00		0.007
			62.00	63.50	227253	1.50		0.011
			63.50	65.00	227254	1.50		0.029
			65.00	66.50	227255	1.50		0.005
			66.50	68.00	227256	1.50		0.013
			68.00	69.50	227257	1.50		0.009
			69.50	71.00	227258	1.50		0.009
			71.00	72.50	227259	1.50		0.024
			72.50	74.00	227260	1.50		0.041
			74.00	75.00	228835	1.00		0.029
			75.00	76.00	228836	1.00		2.290
			76.00	77.00	228837	1.00		0.023
			77.00	78.00	228838	1.00		0.489
			78.00	79.50	227261	1.50		0.490
			79.50	81.00	227262	1.50		0.086
			81.00	82.50	227263	1.50		0.018
			82.50	84.00	227264	1.50		0.008
			84.00	85.00	227265	1.00		0.007
			85.00	86.00	228839	1.00		0.057
			86.00	87.00	228841	1.00		0.049
			87.00	88.00	228842	1.00		0.102
			88.00	89.50	227266	1.50		0.418
			89.50	91.00	227267	1.50		0.148
89.90	93.00	FRC <b>Fractured</b> 40% broken core.	91.00	92.50	227268	1.50		0.060
			92.50	94.00	227269	1.50		0.010
			94.00	95.50	227271	1.50		0.015
			95.50	97.00	227272	1.50		0.132
			97.00	98.00	227273	1.00		0.096
			98.00	99.00	227274	1.00		0.113
			99.00	100.00	228843	1.00		0.007
99.20	111.70	Sl; Pot; Chl <b>Silicification; Potassic alteration; Chloritisation</b> Light silicification and light potassic alteration?. Pervasive						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
99.20	111.70	alteration. Light to moderate chloritisation in fine stringers.  BRE <b>Breccia</b> The core is lightly brecciated.	100.00	101.00	228844	1.00	0.066		0.066
			101.00	102.00	228845	1.00	0.055		0.055
			102.00	103.00	228846	1.00	0.041		0.041
			103.00	104.00	P000096	1.00	0.020		0.020
			104.00	105.00	P000097	1.00	0.018		0.018
			105.00	106.00	P000098	1.00	<0.005		0.001
			106.00	107.00	P000099	1.00	<0.005		0.001
			107.00	108.00	P000100	1.00	0.025		0.025
			108.00	109.00	P000101	1.00	0.052		0.052
			109.00	110.00	P000102	1.00	0.070		0.070
			110.00	111.00	P000103	1.00	0.005		0.005
			111.00	112.00	P000104	1.00	<0.005		0.001
			112.00	113.50	227275	1.50	0.013		0.013
			113.50	115.00	227276	1.50	0.008		0.008
			115.00	116.50	227277	1.50	0.053		0.053
118.00	125.00	Chl <b>Chloritisation</b> Moderate chloritisation in fine stringers.	116.50	118.00	227278	1.50	0.022		0.022
			118.00	119.50	227279	1.50	0.008		0.008
			119.50	121.00	227281	1.50	<0.005		0.001
			121.00	122.50	227282	1.50	0.007		0.007
			122.50	124.00	227283	1.50	0.005		0.005
			124.00	125.50	227284	1.50	0.005		0.005
			125.50	127.00	227285	1.50	<0.005		0.001
			127.00	128.50	227286	1.50	<0.005		0.001
130.00	137.20	Chl; Epi <b>Chloritisation; Epidotisation</b> Moderate pervasive chloritisation alternating with moderate pervasive epidotisation.	128.50	130.00	227287	1.50	0.005		0.005
			130.00	131.50	227288	1.50	0.007		0.007
			131.50	133.00	227289	1.50	0.026		0.026
			133.00	134.50	227291	1.50	0.007		0.007
			134.50	136.00	227292	1.50	0.032		0.032
			136.00	137.00	227293	1.00	0.054		0.054
137.20	169.00	Sil; Epi <b>Silicification; Epidotisation</b> Moderate to high pervasive silicification and epidotisation and	137.00	138.00	P000105	1.00	0.029		0.029
			138.00	139.00	P000106	1.00	0.163		0.163
			139.00	140.00	P000107	1.00	0.242		0.242

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		light to moderate pervasive chloritisation.	140.00	141.00	P000108	1.00	1.000		1.000
			141.00	142.00	P000109	1.00	4.660	4.42	4.420
			142.00	143.00	P000110	1.00	1.060		1.060
137.20	163.60	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite.							
142.50	154.00	STW;2%;Qz;;;Py0.5; <b>Stockwerk 2% Quartz Pyrite0.5%</b> 1-2% smokey Qz veins and injections.	143.00	144.00	P000111	1.00	2.080		2.080
			144.00	145.00	P000113	1.00	1.655		1.655
			145.00	146.00	P000114	1.00	1.780		1.780
			146.00	147.00	P000115	1.00	7.330	7.33	7.330
146.80	147.30	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Intrusive rock. Purple-green aphanitic matrix with 15-20% Lath Fp phenos. Massive and non magnetic.	147.00	148.00	P000116	1.00	1.785		1.785
			148.00	149.00	P000117	1.00	7.560	7.13	7.130
			149.00	150.00	P000118	1.00	2.000		2.000
			150.00	151.00	P000119	1.00	1.125		1.125
		Light chloritisation as fine stringers.	151.00	152.00	P000120	1.00	5.340	5.20	5.200
			152.00	153.00	P000121	1.00	2.320		2.320
		2-3% very fine disseminated pyrite.							
		Sahrp contacts but irregulars (almost 90°)							
152.50	153.00	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Same as 146.8-147.3m.	153.00	154.00	P000122	1.00	1.490		1.490
			154.00	155.00	P000123	1.00	0.028		0.028
			155.00	156.00	P000124	1.00	0.042		0.042
			156.00	157.00	P000125	1.00	0.177		0.177
			157.00	158.00	P000126	1.00	0.187		0.187
			158.00	159.00	P000127	1.00	0.300		0.300
			159.00	160.00	P000128	1.00	1.300		1.300
159.10	159.20	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Same as 146.8-147.3m.							
		Contacts sharp @ 50° TCA.							
159.65	160.15	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Same as 146.8-147.3m.	160.00	161.00	P000130	1.00	2.850		2.850
			161.00	162.00	P000131	1.00	0.907		0.907
			162.00	163.00	P000132	1.00	0.235		0.235
		Contacts sharp @ 50-60° TCA.	163.00	164.00	P000133	1.00	0.013		0.013



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			164.00	165.00	P000134	1.00		0.007		0.007
			165.00	166.50	227294	1.50		0.008		0.008
			166.50	168.00	227295	1.50		0.074		0.074
			168.00	169.50	227296	1.50		0.009		0.009
169.00	181.70	Chl; Epi <b>Chloritisation; Epidotisation</b> Moderate to high pervasive chloritisation and epidotisation.	169.50	171.00	227297	1.50		0.011		0.011
			171.00	172.50	227298	1.50		0.011		0.011
171.90	172.30	BRE <b>Breccia</b> Angular syenite fragments is a chloritic matrix.	172.50	174.00	227299	1.50		0.014		0.014
			174.00	175.50	227300	1.50		0.011		0.011
			175.50	177.00	227301	1.50		0.010		0.010
			177.00	178.50	227302	1.50		0.013		0.013
			178.50	180.00	227303	1.50		1.630		1.630
			180.00	181.50	227304	1.50		0.531		0.531
181.40	183.00	BRE <b>Breccia</b> Angular syenite fragments in a chloritic matrix.	181.50	183.00	227305	1.50		0.472		0.472
			183.00	184.00	227306	1.00		0.248		0.248
			184.00	185.00	P000135	1.00		0.062		0.062
			185.00	186.00	P000136	1.00		0.205		0.205
			186.00	187.00	P000137	1.00		0.031		0.031
			187.00	188.00	P000138	1.00		0.124		0.124
			188.00	189.00	P000139	1.00		0.017		0.017
			189.00	190.00	P000140	1.00		0.165		0.165
			190.00	191.50	227307	1.50		0.031		0.031
			191.50	193.00	227308	1.50		1.855		1.855
			193.00	194.50	227309	1.50		0.682		0.682
194.10	221.50	S <b>Sediment (Meta incl.)</b> Sedimentary rock. Grey-greenish fine grained to aphanitic matrix. Foliated @ 60° TCA, homogenous, and non magnetic. Bands cm of conglomerats (felsic pale rounded fragments in a grey matrix, no contacts between conгло and greywacke)  Tr-1% Qz-Cc veins @ 30° TCA.  Light pervasive chloritisation and local light sericitisation.  Tr-1% (loc 3%) very fine to fine disseminated pyrite.	194.50	196.00	227311	1.50		0.128		0.128
			196.00	197.00	227312	1.00		0.298		0.298
			197.00	198.00	P000141	1.00		1.050		1.050
			198.00	199.00	P000142	1.00		0.011		0.011
			199.00	200.50	227313	1.50		0.010		0.010
			200.50	202.00	227314	1.50		0.012		0.012
			202.00	203.50	227315	1.50		0.011		0.011
			203.50	205.00	227316	1.50		0.014		0.014
			205.00	206.50	227317	1.50		0.016		0.016
			206.50	208.00	227318	1.50		0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
194.10      197.00      Ser <b>Sericitisation</b> Light pervasive sericitisation.	208.00	209.50	227319	1.50	0.011		0.011
	209.50	211.00	227320	1.50	0.019		0.019
	211.00	212.50	227321	1.50	0.016		0.016
	212.50	214.00	227322	1.50	0.009		0.009
	214.00	215.50	227323	1.50	0.009		0.009
	215.50	217.00	227324	1.50	0.008		0.008
	217.00	218.50	227325	1.50	0.009		0.009
	218.50	220.00	227326	1.50	0.006		0.006
	220.00	221.50	227327	1.50	0.007		0.007
221.50	Fin du sondage Nombre d'échantillons : 173 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 215.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	7.50	227230	O54Pa	1.50	2.880	2.880
19.50	21.00	227240	m	1.50	0.008	0.008
42.00	43.50	227250	O52Pb	1.50	0.314	0.314
56.00	57.00	P000094	O53Pb	1.00	0.656	0.656
58.00	59.00	228831	O61d	1.00	0.324	0.324
85.00	86.00	228840	228839	1.00	0.058	0.058
92.50	94.00	227270	O53Pb	1.50	0.643	0.643
118.00	119.50	227280	m	1.50	<0.005	0.001
131.50	133.00	227290	O54Pa	1.50	2.980	2.980
143.00	144.00	P000112	O54Pa	1.00	3.030	3.020
159.00	160.00	P000129	O52Pb	1.00	0.334	0.334
193.00	194.50	227310	O52Pb	1.50	0.317	0.317



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.60	MT <b>Casing</b> Casing							
3.60	228.00	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Dark red-green, pink. Several Quartz veins (3%) oriented in foliation. Lots of fractures (10-15%) filled with silica-carbonate fluids, boudinage. Patches of potassic alteration. Fld euhedral phenos (20% to 40%) (2-3mm) weakly CL and ALB altered. Lath Fld (5% to 10%) (3mmX5mm). Fine to medium grains. Locally breccia intervals (=5 to 10cm)  Sections with strong epidotisation (17.5m-18.6m---24.0m-26.3m- --30.45m-32.1m---33.6m-34.7m---36.1m-36.5m---40.0m-47.2m----107.9m-142.9m---150.1-150.5m). Pervasive Weathering (rust, orange color) and sericite.  Strong Foliation 30-40 TCA. Sharp lower contact 40 TCA.  Alterations : Weak epidote, strong pervasive potassic, medium ALB, medium SR, medium CARB and strong CL. Micro-fractures filled with chlorite after 45m.  Fine disseminated Py (1%) to no mineralization. Magnetisme: 3.6m-48m (Mag +), 48m-105m (Mag+++), 105m-176m (Mag+), 176m-196.6m (Mag+++ and 209m-250.6m (Mag+++).	3.60	4.60	D952732	1.00	0.005		0.005
			4.60	6.00	D952733	1.40	0.006		0.006
			6.00	7.50	D952734	1.50	<0.005		0.001
7.40	7.45	VEI;5;Qz;T;40°; <b>Vein 5 Quartz Tension 40°</b> quartz vein							
7.50	7.57	VEI;7;Qz;T;50°; <b>Vein 7 Quartz Tension 50°</b> qtz vein	7.50	9.00	D952735	1.50	<0.005		0.001
			9.00	10.50	D952736	1.50	0.011		0.011
			10.50	12.00	D952737	1.50	0.009		0.009
			12.00	13.50	D952738	1.50	0.030		0.030
			13.50	15.00	D952739	1.50	<0.005		0.001
			15.00	16.50	D952741	1.50	<0.005		0.001
			16.50	17.00	P003778	0.50	0.017		0.017
			17.00	18.00	P003779	1.00	0.217		0.217

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
17.50	18.60	Epi70; Chl25; Ser20 <b>Epidotisation 70; Chloritisation 25; Sericitisation 20</b> strong alteration						
17.50	18.60	FRC; FOL <b>Fractured 50°; Foliation</b> Strong foliation and fracture	18.00	19.00	P003780	1.00	0.192	0.192
			19.00	19.50	P003781	0.50	<0.005	0.001
			19.50	21.00	D952742	1.50	0.189	0.189
			21.00	22.50	D952743	1.50	0.405	0.405
			22.50	24.00	D952744	1.50	0.044	0.044
24.00	26.30	Epi70; Chl30; Ser30; Wea15 <b>Epidotisation 70; Chloritisation 30; Sericitisation 30;</b> <b>Weathering (Incl. Saproilitic alter.) 15</b> strong alt	24.00	25.00	P003782	1.00	0.318	0.318
			25.00	26.00	P003783	1.00	0.125	0.125
			26.00	27.00	D952746	1.00	<0.005	0.001
			27.00	28.50	D952747	1.50	0.014	0.014
			28.50	30.00	D952748	1.50	0.033	0.033
			30.00	31.00	D952749	1.00	0.054	0.054
30.45	32.10	Epi70; Blch20; Chl30; Ser30; FCT10; Wea30 <b>Epidotisation 70; Bleaching 20; Chloritisation 30;</b> <b>Sericitisation 30; Fuchsitization 10; Weathering (Incl. Saproilitic alter.) 30</b> strong alt	31.00	32.00	P003784	1.00	<0.005	0.001
			32.00	33.20	D952751	1.20	0.005	0.005
			33.20	34.20	P003785	1.00	0.186	0.186
33.40	34.70	Epi70; Blch30; Chl30; FCT15 <b>Epidotisation 70; Bleaching 30; Chloritisation 30;</b> <b>Fuchsitization 15</b> strong alt	34.20	34.70	P003787	0.50	0.927	0.927
			34.70	36.00	D952752	1.30	0.008	0.008
			36.00	36.60	P003788	0.60	0.190	0.190
36.10	36.50	Epi50; Chl50 <b>Epidotisation 50; Chloritisation 50</b> strong alt	36.60	37.60	D952753	1.00	0.025	0.025
			37.60	39.00	D952754	1.40	0.093	0.093
38.00	38.60	FRC <b>Fractured 20°</b> fracture	39.00	40.00	P003789	1.00	0.042	0.042
40.00	47.20	Epi70; FCT15; Chl40; Wea25; Ser14; Alb10 <b>Epidotisation 70; Fuchsitization 15; Chloritisation 40;</b> <b>Weathering (Incl. Saproilitic alter.) 25; Sericitisation 14; Albisation 10</b> strong alt	40.00	41.00	D952755	1.00	0.066	0.066
			41.00	42.00	D952756	1.00	0.035	0.035
			42.00	43.00	D952757	1.00	0.301	0.301
42.80	43.60	FAI <b>Fault 10°</b> fault	43.00	44.00	D952758	1.00	0.026	0.026
			44.00	45.00	P003790	1.00	0.042	0.042
			45.00	46.50	D952759	1.50	0.017	0.017

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			46.50	47.50	P003791	1.00		0.020		0.020
			47.50	49.00	D952761	1.50		0.023		0.023
			49.00	50.50	D952762	1.50		0.031		0.031
			50.50	52.00	D952763	1.50		0.329		0.329
51.70	52.50	FAI Fault 00° falut	52.00	53.00	D952764	1.00		0.472		0.472
52.50	88.70	FOL Foliation 30° fol30	53.00	54.00	D952765	1.00		0.117		0.117
			54.00	55.00	P003792	1.00		0.547		0.547
			55.00	56.00	P003793	1.00		2.870		2.870
			56.00	57.00	P003794	1.00		2.060		2.060
			57.00	58.00	P003795	1.00		0.620		0.620
			58.00	59.00	D952766	1.00		0.201		0.201
			59.00	60.00	D952767	1.00		0.025		0.025
			60.00	61.50	D952768	1.50		0.045		0.045
			61.50	63.00	D952769	1.50		0.007		0.007
			63.00	64.50	D952771	1.50		<0.005		0.001
			64.50	66.00	D952772	1.50		<0.005		0.001
			66.00	67.50	D952773	1.50		0.006		0.006
			67.50	69.00	D952774	1.50		0.021		0.021
			69.00	70.50	D952775	1.50		0.007		0.007
			70.50	72.00	D952776	1.50		<0.005		0.001
			72.00	73.50	D952777	1.50		0.022		0.022
			73.50	75.00	D952778	1.50		0.008		0.008
			75.00	76.50	D952779	1.50		0.011		0.011
			76.50	78.00	D952781	1.50		<0.005		0.001
			78.00	79.50	D952782	1.50		0.006		0.006
			79.50	81.00	D952783	1.50		<0.005		0.001
			81.00	82.00	D952784	1.00		0.026		0.026
			82.00	83.00	D952786	1.00		0.053		0.053
			83.00	84.00	P003796	1.00		0.011		0.011
			84.00	85.50	D952787	1.50		<0.005		0.001
			85.50	87.00	D952788	1.50		0.005		0.005
			87.00	88.50	D952789	1.50		0.014		0.014

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
88.70	88.90	FRC <b>Fractured 30°</b> fracture	88.50	90.00	D952791	1.50	0.042		0.042
			90.00	91.50	D952792	1.50	0.016		0.016
			91.50	93.00	D952793	1.50	<0.005		0.001
			93.00	94.50	D952794	1.50	<0.005		0.001
			94.50	96.00	D952795	1.50	<0.005		0.001
			96.00	97.50	D952796	1.50	<0.005		0.001
			97.50	99.00	D952797	1.50	<0.005		0.001
			99.00	100.50	D952798	1.50	0.005		0.005
			100.50	101.50	D952799	1.00	<0.005		0.001
			101.50	102.50	P003797	1.00	0.005		0.005
			102.50	103.50	D952801	1.00	<0.005		0.001
			103.50	105.00	D952802	1.50	<0.005		0.001
			105.00	106.00	D952803	1.00	<0.005		0.001
			106.00	107.00	D952804	1.00	<0.005		0.001
107.90	142.90	Epi70; Chi40; Alb10; Sil30; Ser15 <b>Epidotisation 70; Chloritisation 40; Albitisation 10;</b> <b>Silicification 30; Sericitisation 15</b> strong alteration	107.00	108.00	P003798	1.00	0.052		0.052
			108.00	109.00	D952805	1.00	0.064		0.064
108.70	108.85	VEI;15;Qz;T;10°;; <b>Vein 15 Quartz Tension 10°</b> qtz vein	109.00	110.00	D952806	1.00	0.927		0.927
			110.00	111.00	P003799	1.00	0.675		0.675
110.40	111.40	VEI;100;Qz;T;;; <b>Vein 100 Quartz Tension</b> qtz vein	111.00	112.00	P003800	1.00	0.159		0.159
111.60	111.80	VEI;3;Qz;T;20°;; <b>Vein 3 Quartz Tension 20°</b> qtz vein	112.00	113.00	P003801	1.00	0.220		0.220
112.20	112.40	VEI;5;Qz;T;;; <b>Vein 5 Quartz Tension</b> qtz vein							
112.70	112.90	VEI;15;;T;20°;; <b>Vein 15 Tension 20°</b> qtz vein	113.00	114.00	D952807	1.00	0.183		0.183
			114.00	115.00	P003802	1.00	0.047		0.047
			115.00	116.00	D952808	1.00	0.010		0.010
			116.00	117.00	D952809	1.00	0.010		0.010
			117.00	118.00	P003803	1.00	0.384		0.384



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			118.00	119.00	D952811	1.00		0.113	0.113
			119.00	120.00	D952812	1.00		0.143	0.143
			120.00	121.60	D952813	1.60		0.074	0.074
			121.60	122.60	P003804	1.00		0.140	0.140
			122.60	123.60	P003805	1.00		0.032	0.032
			123.60	124.60	D952814	1.00		0.022	0.022
			124.60	126.00	D952815	1.40		0.005	0.005
			126.00	127.50	D952816	1.50		<0.005	0.001
			127.50	128.50	D952818	1.00		0.007	0.007
			128.50	130.00	D952819	1.50		0.067	0.067
			130.00	131.00	P003806	1.00		0.083	0.083
			131.00	132.00	P003807	1.00		0.050	0.050
			132.00	133.50	D952821	1.50		0.008	0.008
			133.50	135.00	D952822	1.50		0.008	0.008
			135.00	136.00	P003808	1.00		0.005	0.005
			136.00	137.00	D952823	1.00		<0.005	0.001
			137.00	138.00	D952824	1.00		0.006	0.006
			138.00	139.50	D952825	1.50		0.012	0.012
			139.50	141.00	D952826	1.50		0.056	0.056
141.00	156.00	FOL	141.00	142.00	D952827	1.00		0.008	0.008
		<b>Foliation 45°</b>	142.00	143.00	P003810	1.00		0.006	0.006
		foliation	143.00	144.00	P003811	1.00		<0.005	0.001
			144.00	145.50	D952828	1.50		0.005	0.005
			145.50	147.00	D952829	1.50		<0.005	0.001
			147.00	148.50	D952831	1.50		0.005	0.005
			148.50	150.00	D952832	1.50		<0.005	0.001
			150.00	151.50	D952833	1.50		0.005	0.005
150.10	150.50	Epi60; Chi60	151.50	153.00	D952834	1.50		<0.005	0.001
		<b>Epidotisation 60; Chloritisation 60</b>	153.00	154.50	D952835	1.50		<0.005	0.001
		strong alt	154.50	156.00	D952836	1.50		0.022	0.022
			156.00	157.50	D952837	1.50		0.046	0.046
			157.50	159.00	D952838	1.50		0.055	0.055
			159.00	160.70	D952839	1.70		0.009	0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
161.20	162.10	BSF <b>Breccia silicified zone</b> Breccia. Gray to dark gray green. Strong silicification and chloritisation.  Matrix is quartz. 20% smokey quartz. 1-2% disseminated and stringers Py. Sharp upper contact 40 TCA and lower contact 40 TCA.	160.70	161.20	P003812	0.50	0.186		0.186
			161.20	162.10	P003813	0.90	2.500		2.500
			162.10	162.60	P003814	0.50	0.417		0.417
			162.60	164.00	D952841	1.40	0.114		0.114
			164.00	165.00	P003815	1.00	0.267		0.267
			165.00	166.00	P003816	1.00	1.090		1.090
			166.00	167.00	P003817	1.00	0.164		0.164
			167.00	167.50	P003818	0.50	0.106		0.106
			167.50	167.90	P003819	0.40	1.060		1.060
			167.90	168.40	P003820	0.50	0.057		0.057
			168.40	169.50	D952842	1.10	0.005		0.005
			169.50	171.00	D952843	1.50	<0.005		0.001
			171.00	172.50	D952844	1.50	0.009		0.009
			172.50	174.00	D952846	1.50	<0.005		0.001
			174.00	175.50	D952847	1.50	<0.005		0.001
			175.50	177.00	D952848	1.50	<0.005		0.001
			177.00	178.50	D952849	1.50	0.005		0.005
			178.50	180.00	D952851	1.50	<0.005		0.001
			180.00	181.50	D952852	1.50	0.005		0.005
			181.50	183.00	D952853	1.50	<0.005		0.001
183.00	184.50	D952854	1.50	<0.005		0.001			
184.50	186.00	D952855	1.50	<0.005		0.001			
186.00	187.50	D952856	1.50	<0.005		0.001			
187.50	189.00	D952857	1.50	0.007		0.007			
189.00	190.50	D952858	1.50	0.006		0.006			
190.50	192.00	D952859	1.50	0.016		0.016			
192.00	193.50	D952861	1.50	0.033		0.033			
193.50	195.00	D952862	1.50	0.025		0.025			
195.00	196.00	D952863	1.00	<0.005		0.001			
196.00	197.00	P003821	1.00	0.624		0.624			
196.60	209.00	B <b>Breccia</b> Breccia. Gray. Intense silicification, medium epidotisation, medium CL, medium carbonatation, medium albitisation weak							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
196.60	209.00	<p>fuschite and medium pervasive potassic. 30% Fld phenos.</p> <p>Moderate fractures (30%) filled with silica-carbonate fluids.</p> <p>Matrix silica and carbonate. 3-5% stringers and disseminated Py. Upper contact 40 TCA.</p> <p>Py05; Py03</p> <p><b>Pyrite 05%; Pyrite 03%</b></p> <p>3-5% disseminated Py</p>	197.00	198.00	P003822	1.00	1.450	6.54	1.450
			198.00	199.00	P003823	1.00	1.900		1.900
			199.00	200.00	P003824	1.00	6.080		6.540
			200.00	201.00	P003825	1.00	0.691		0.691
			201.00	202.00	P003826	1.00	2.720		2.720
			202.00	203.00	P003827	1.00	4.320		4.320
			203.00	204.00	P003828	1.00	1.765		1.765
			204.00	205.00	P003829	1.00	1.690		1.690
			205.00	206.00	P003830	1.00	1.135		1.135
			206.00	207.00	P003831	1.00	1.125		1.125
			207.00	208.00	P003833	1.00	0.696		0.696
			208.00	209.00	P003834	1.00	1.475		1.475
			209.00	210.00	P003835	1.00	0.556		0.556
			210.00	211.50	D952864	1.50	0.162		0.162
			211.50	213.00	D952865	1.50	0.011		0.011
			213.00	214.50	D952866	1.50	<0.005		0.001
			214.50	216.00	D952867	1.50	0.104		0.104
			216.00	217.70	D952868	1.70	0.152		0.152
			217.70	219.20	P003934	1.50	0.147		0.147
			219.20	220.70	P003935	1.50	0.065		0.065
219.60	222.30	<p>APH; MAS</p> <p><b>Aphanitic; Massive rock</b></p> <p>Dark green. Aphanitic to fine grains.Strong foliation 40TCA.</p> <p>Sharp upper and lower contacts 40 TCA. Strong CH alteration, medium CARB, medium SR. 5% fractures filled with silica fluid.</p> <p>Tr. of disseminated Py.Mag +++.</p>	220.70	222.20	P003936	1.50	0.063	0.063	
			222.20	223.20	P003836	1.00	1.470	1.470	
222.30	228.00	<p>B</p> <p><b>Breccia</b></p> <p>Same as 196m to 209m</p>							
222.30	228.00	Py03	223.20	224.20	P003837	1.00	0.638	0.638	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Pyrite 03% 3% disseminated Py	224.20	225.20	P003838	1.00	0.540		0.540
			225.20	226.00	P003839	0.80	0.560		0.560
			226.00	227.00	P003840	1.00	0.914		0.914
			227.00	228.00	P003841	1.00	0.948		0.948
228.00	270.90	BA; APH	228.00	229.00	P003842	1.00	1.925		1.925
		<b>Basalt; Aphanitic</b>	229.00	230.00	D952869	1.00	0.314		0.314
		Dark green. Melanocratic. Aphanitic to fine grains.Strong foliation	230.00	231.00	D952871	1.00	0.005		0.005
		40TCA. Sharp upper and lower contacts 40 TCA. Strong CH	231.00	232.50	D952872	1.50	0.006		0.006
		alteration, medium SR. medium CARB and pervasive medium	232.50	234.00	D952873	1.50	<0.005		0.001
		Epidotisation. Few fractures filled with silica fluid. No mineralization	234.00	235.50	D952874	1.50	<0.005		0.001
		.Magnetite disseminated (25%). Mag +++.	235.50	237.00	D952875	1.50	0.016		0.016
		From 265.5m to 270.9 : Mesocratic. Aphanitic, medium sericite	237.00	238.50	D952876	1.50	0.048		0.048
		alteration and strong CH.	238.50	240.00	D952877	1.50	<0.005		0.001
			240.00	241.50	D952878	1.50	0.009		0.009
			241.50	243.00	D952879	1.50	<0.005		0.001
			243.00	244.50	D952881	1.50	<0.005		0.001
			244.50	246.00	D952882	1.50	<0.005		0.001
			246.00	247.50	D952883	1.50	<0.005		0.001
			247.50	249.00	D952884	1.50	<0.005		0.001
			249.00	250.50	D952886	1.50	<0.005		0.001
			250.50	252.00	D952887	1.50	<0.005		0.001
			252.00	253.50	D952888	1.50	<0.005		0.001
			253.50	255.00	D952889	1.50	<0.005		0.001
			255.00	256.50	D952891	1.50	<0.005		0.001
			256.50	258.00	D952892	1.50	0.005		0.005
			258.00	259.50	D952893	1.50	<0.005		0.001
			259.50	261.00	D952894	1.50	<0.005		0.001
			261.00	262.50	D952895	1.50	<0.005		0.001
			262.50	264.00	D952896	1.50	<0.005		0.001
			264.00	265.50	D952897	1.50	<0.005		0.001
			265.50	267.00	D952898	1.50	<0.005		0.001
			267.00	268.50	D952899	1.50	<0.005		0.001
			268.50	270.00	D952901	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
270.90	281.60	TZ; APH <b>Transitional Zone; Aphanitic</b> Transitionnal Syenite, yellowish-gray with some dark gray intervals. Felsic. Aphanitic. 2-5% of mm fractures filled with CL. Foliation 40TCA. Strong Sericite alteration, moderate CL and moderate bleaching . Phenos are disappearing. Phenos of magnetite (3-6mm). Locally cm to dm bands of felsic Tuf. Traces of Py and Cp. Upper gradational and lower sharp contact 30 TCA. Mag +++++.	270.00	270.90	P003843	0.90	0.007		0.007
			270.90	271.80	P003844	0.90	0.487		0.487
			271.80	273.00	D952902	1.20	<0.005		0.001
			273.00	274.00	D952903	1.00	<0.005		0.001
			274.00	275.00	D952904	1.00	0.008		0.008
			275.00	276.00	P003888	1.00	0.212		0.212
			276.00	277.50	D952905	1.50	0.367		0.367
			277.50	279.00	D952906	1.50	0.091		0.091
			279.00	280.50	D952907	1.50	0.018		0.018
			280.50	282.00	D952908	1.50	0.005		0.005
281.60	513.70	SY PT POR; PT; POR <b>Syenite Lath Porphyry Intrusive; Lath; Porphyric</b> Dark red to dark red-green, purple. Fld lath (15-20%) 3-5mm X 5-10mm. Fld moderate ALB and CL. Fine to medium grains. Lots of mm fractures filled with chlorite (5%) and with silica-carbonate fluids (10%). Strong pervasive epidote alteration, moderate potassic, weak pervasive HEM and moderate CL. Locally stockwork. Disseminated magnetite (10%). Mag +++. Foliation 60 TCA. Trace to no mineralization. Upper contact sharp 30 TCA and lower gradational contact.  From 480.4m to 514.8m : MNZD 1-5% disseminated Py and stringers, tr of Pyrrhothite + 30% stockworks and micro fractures filled with CL.	282.00	283.50	D952909	1.50	<0.005		0.001
			283.50	285.00	D952911	1.50	<0.005		0.001
			285.00	286.00	D952912	1.00	<0.005		0.001
			286.00	287.10	D952913	1.10	<0.005		0.001
			287.10	287.60	P003845	0.50	<0.005		0.001
			287.60	288.60	P003846	1.00	<0.005		0.001
			288.60	289.60	P003847	1.00	<0.005		0.001
			289.60	290.60	P003848	1.00	<0.005		0.001
			290.60	291.60	P003849	1.00	<0.005		0.001
			291.60	292.60	D952914	1.00	0.015		0.015
			292.60	294.00	D952915	1.40	0.009		0.009
			294.00	295.50	D952916	1.50	<0.005		0.001
			295.50	297.00	D952917	1.50	0.015		0.015
			297.00	298.50	D952918	1.50	0.032		0.032
			298.50	300.00	D952919	1.50	<0.005		0.001
			300.00	301.50	D952921	1.50	0.008		0.008
			301.50	303.00	D952922	1.50	0.005		0.005
			303.00	304.00	D952923	1.00	<0.005		0.001
304.00	305.00	P003851	1.00	0.006		0.006			
305.00	306.00	P003852	1.00	0.010		0.010			
306.00	307.00	P003853	1.00	0.006		0.006			
307.00	308.00	D952924	1.00	<0.005		0.001			
308.00	309.00	D952925	1.00	0.033		0.033			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			309.00	310.50	D952926	1.50	<0.005		0.001
			310.50	312.00	D952927	1.50	<0.005		0.001
			312.00	313.50	D952928	1.50	0.009		0.009
			313.50	315.00	D952929	1.50	0.006		0.006
			315.00	316.00	D952931	1.00	0.012		0.012
			316.00	317.00	P003854	1.00	<0.005		0.001
			317.00	318.00	P003855	1.00	<0.005		0.001
			318.00	319.00	P003856	1.00	0.009		0.009
			319.00	320.00	D952932	1.00	0.008		0.008
			320.00	321.00	D952933	1.00	<0.005		0.001
			321.00	322.50	D952934	1.50	<0.005		0.001
			322.50	324.00	D952935	1.50	0.010		0.010
			324.00	325.50	D952936	1.50	<0.005		0.001
			325.50	327.00	D952937	1.50	<0.005		0.001
			327.00	328.50	D952938	1.50	<0.005		0.001
			328.50	330.00	D952939	1.50	<0.005		0.001
			330.00	331.50	D952941	1.50	<0.005		0.001
			331.50	333.00	D952942	1.50	<0.005		0.001
			333.00	334.50	D952943	1.50	0.005		0.005
281.60	315.00	FOL <b>Foliation 60°</b> fol60							
334.00	345.60	Epi40; Ser25 <b>Epidotisation 40; Sericitisation 25</b> strong epidotisation and medium SR	334.50	336.00	D952944	1.50	0.038		0.038
			336.00	337.50	D952946	1.50	0.022		0.022
336.60	337.20	B; POR <b>Breccia; Porphyric</b> Red-yellow-black. Matrix quartz and chlorite. Fld phenos (70%) (5-10mm). Medium SI, medium SR and medium CL alteration. No mineralization. Sharp contact 20 TCA.	337.50	339.00	D952947	1.50	0.023		0.023
			339.00	340.50	D952948	1.50	0.031		0.031
340.10	341.70	B; POR <b>Breccia; Porphyric</b> Red-yellow-black. Matrix quartz and chlorite. Fld phenos (60%) (2-3mm). Medium SI, medium SR and medium CL alteration. No mineralization. Sharp contact 20 TCA.	340.50	342.00	D952949	1.50	0.286		0.286
			342.00	343.50	D952951	1.50	0.028		0.028
			343.50	345.00	D952952	1.50	0.012		0.012
			345.00	346.50	D952953	1.50	<0.005		0.001
			346.50	348.00	D952954	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
349.10	353.20	ChI60; Epi30 <b>Chloritisation 60; Epidotisation 30</b> strong alt	348.00	349.50	D952955	1.50	<0.005		0.001
			349.50	351.00	D952956	1.50	<0.005		0.001
349.80	350.60	B; POR <b>Breccia; Porphyric</b> Green-pink-black. Matrix silica and chlorite. Fld and quartz phenos (60%) (10-15mm0mm). Medium SI, medium SR, medium potassic and strong CL alteration. Tr of disseminated Py. Sharp upper and lower contact 50 TCA.	351.00	352.00	D952957	1.00	<0.005		0.001
			352.00	353.00	P003857	1.00	0.005		0.005
			353.00	354.00	P003858	1.00	0.012		0.012
353.40	381.10	TZ; B; I2D; V3 <b>Transitional Zone; Breccia; Syenite; Mafic</b> <b>Meta-Volcanic</b> Mixed unit of altered syenite, mafic meta-volcanic and breccia. Dark green-gray-. Locally bleached. Breccia texture with Fld (5mm-20mm) (15-30%). Phenos in syenite completely altered (phantom). Aphanitic to fine grains. Fractures (mm) filled with chlorite and silica-carbonate fluid.  Alterations: medium SI, strong CL, medium EPI, weak CARB.  Matrix silica-carbonate albitized. Strong foliation 50 TCA. Locally trace of Py. Upper contact 40 TCA and lower contact 50 TCA. Mag +++++.	354.00	355.00	P003859	1.00	<0.005		0.001
			355.00	356.00	D952958	1.00	0.007		0.007
			356.00	357.00	D952959	1.00	<0.005		0.001
			357.00	358.00	P003860	1.00	0.005		0.005
			358.00	359.00	D952961	1.00	0.014		0.014
358.82	359.00	VEI;;QzAb;T;70°; <b>Vein Quartz Albite Tension 70°</b> quartz vein	359.00	360.00	D952962	1.00	0.006		0.006
			360.00	361.50	D952963	1.50	0.005		0.005
			361.50	363.00	D952964	1.50	0.005		0.005
			363.00	364.50	D952965	1.50	<0.005		0.001
			364.50	366.00	D952966	1.50	0.010		0.010
			366.00	367.50	D952967	1.50	0.014		0.014
			367.50	369.00	D952968	1.50	<0.005		0.001
369.00	379.60	FRC <b>Fractured 50°</b> Lots of fractures in this interval	369.00	370.50	D952969	1.50	0.005		0.005
			370.50	372.00	D952971	1.50	<0.005		0.001
			372.00	373.50	D952972	1.50	<0.005		0.001
			373.50	375.00	D952973	1.50	<0.005		0.001
			375.00	376.00	D952974	1.00	0.005		0.005
			376.00	377.00	D952975	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			377.00	378.00	P003861	1.00		0.011		0.011
			378.00	379.50	D952976	1.50		0.009		0.009
			379.50	381.00	D952977	1.50		0.008		0.008
379.60	380.00	FRC <b>Fractured 50°</b> fracture and broken core								
380.40	381.00	FRC <b>Fractured</b> fracture and broken core	381.00	382.50	D952978	1.50		0.276		0.276
			382.50	384.00	D952979	1.50		0.729		0.729
			384.00	385.50	D952981	1.50		0.396		0.396
			385.50	387.00	D952982	1.50		0.792		0.792
			387.00	388.00	D952983	1.00		0.135		0.135
			388.00	389.00	D952984	1.00		0.284		0.284
			389.00	389.90	P003862	0.90		0.174		0.174
			389.90	390.40	P003863	0.50		0.826		0.826
			390.40	391.40	P003864	1.00		0.112		0.112
			391.40	393.00	D952986	1.60		0.486		0.486
			393.00	394.50	D952987	1.50		0.058		0.058
			394.50	396.00	D952988	1.50		0.080		0.080
			396.00	397.50	D952989	1.50		0.114		0.114
			397.50	399.00	D952991	1.50		0.009		0.009
			399.00	400.20	D952992	1.20		0.010		0.010
			400.20	401.00	P003865	0.80		0.084		0.084
			401.00	402.00	D952993	1.00		0.006		0.006
			402.00	403.50	D952994	1.50		<0.005		0.001
			403.50	405.00	D952995	1.50		0.039		0.039
			405.00	406.50	D952996	1.50		0.014		0.014
			406.50	408.00	D952997	1.50		<0.005		0.001
			408.00	409.50	D952998	1.50		0.052		0.052
			409.50	411.00	D952999	1.50		0.159		0.159
			411.00	412.50	D953001	1.50		0.194		0.194
			412.50	413.60	D953002	1.10		0.031		0.031
			413.60	414.60	P003866	1.00		0.121		0.121
			414.60	415.60	P003867	1.00		0.048		0.048
			415.60	416.60	P003868	1.00		0.005		0.005



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	416.60	417.60	P003869	1.00	0.017		0.017
	417.60	418.60	P003870	1.00	0.020		0.020
	418.60	419.60	P003871	1.00	0.042		0.042
	419.60	420.60	P003872	1.00	0.103		0.103
	420.60	421.60	P003874	1.00	0.050		0.050
	421.60	422.60	P003875	1.00	0.017		0.017
	422.60	424.00	D953003	1.40	0.011		0.011
	424.00	425.00	D953004	1.00	<0.005		0.001
	425.00	426.00	D953005	1.00	<0.005		0.001
	426.00	427.50	D953006	1.50	<0.005		0.001
	427.50	429.00	D953007	1.50	<0.005		0.001
	429.00	430.50	D953008	1.50	<0.005		0.001
	430.50	432.00	D953009	1.50	0.007		0.007
	432.00	432.60	P003876	0.60	0.016		0.016
	432.60	433.60	P003877	1.00	0.841		0.841
	433.60	434.60	P003878	1.00	0.540		0.540
	434.60	435.60	P003879	1.00	0.444		0.444
	435.60	436.60	P003880	1.00	0.167		0.167
	436.60	438.00	D953011	1.40	0.556		0.556
	438.00	439.50	D953012	1.50	0.564		0.564
	439.50	441.00	D953013	1.50	0.080		0.080
	441.00	442.50	D953014	1.50	0.749		0.749
	442.50	444.00	D953015	1.50	0.216		0.216
	444.00	445.00	P003881	1.00	0.084		0.084
	445.00	446.00	P003882	1.00	0.552		0.552
	446.00	447.00	P003883	1.00	0.154		0.154
	447.00	448.50	D953016	1.50	0.202		0.202
	448.50	450.00	D953017	1.50	0.113		0.113
	450.00	451.50	D953018	1.50	0.252		0.252
	451.50	453.00	D953019	1.50	0.235		0.235
	453.00	454.50	D953021	1.50	0.022		0.022
	454.50	456.00	D953022	1.50	0.019		0.019
	456.00	457.50	D953023	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			457.50	459.00	D953024	1.50		0.006	0.006
			459.00	460.50	D953025	1.50		0.037	0.037
			460.50	462.00	D953026	1.50		0.099	0.099
			462.00	463.00	P003884	1.00		<0.005	0.001
			463.00	464.00	P003885	1.00		<0.005	0.001
463.60	465.40	FRC	464.00	465.00	P003887	1.00		<0.005	0.001
		<b>Fractured</b>	465.00	466.50	D953027	1.50		<0.005	0.001
		Fractured and broken core	466.50	468.00	D953028	1.50		<0.005	0.001
			468.00	469.50	D953029	1.50		0.037	0.037
			469.50	471.00	D953031	1.50		0.075	0.075
			471.00	472.00	D953032	1.00		0.102	0.102
471.90	480.40	Epi40; Ser40; Sil50; Alb25	472.00	473.00	P003889	1.00		0.385	0.385
		<b>Epidotisation 40; Sericitisation 40; Silicification 50;</b>	473.00	474.00	P003890	1.00		0.376	0.376
		<b>Albitisation 25</b>	474.00	475.00	P003891	1.00		0.049	0.049
		strong alterations	475.00	476.00	P003892	1.00		0.280	0.280
			476.00	477.00	P003893	1.00		0.538	0.538
476.90	500.00	Py03; Py05	477.00	478.00	P003894	1.00		0.761	0.761
		<b>Pyrite 03%; Pyrite 05%</b>	478.00	479.00	P003895	1.00		1.780	1.780
		3% to 5% disseminated Py and stringers + tr of Pyrothite	479.00	480.00	P003896	1.00		1.230	1.230
			480.00	481.00	P003897	1.00		0.348	0.348
480.40	496.00	Sil70; Epi30; Alb20; Chl30	481.00	482.00	P003898	1.00		1.525	1.525
		<b>Silicification 70; Epidotisation 30; Albitisation 20;</b>	482.00	483.00	P003899	1.00		0.413	0.413
		<b>Chloritisation 30</b>	483.00	484.00	P003900	1.00		0.769	0.769
		strong alterations	484.00	485.00	P003901	1.00		1.580	1.580
			485.00	486.00	P003902	1.00		2.830	2.830
			486.00	487.00	P003903	1.00		0.700	0.700
			487.00	488.00	P003904	1.00		1.975	1.975
			488.00	489.00	P003905	1.00		0.855	0.855
			489.00	490.00	P003906	1.00		1.250	1.250
			490.00	491.00	P003907	1.00		1.035	1.035
			491.00	492.00	P003908	1.00		0.381	0.381
			492.00	493.00	P003909	1.00	3.65	3.720	3.650
			493.00	494.00	P003910	1.00		0.377	0.377

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
496.00	513.70	Chl50; Epi10; Ser10; Sil10 <b>Chloritisation 50; Epidotisation 10; Sericitisation 10;</b> <b>Silicification 10</b> Strong alterations	494.00	495.00	P003912	1.00	0.827		0.827
			495.00	496.00	P003913	1.00	0.280		0.280
			496.00	497.00	P003914	1.00	0.042		0.042
			497.00	498.00	P003915	1.00	0.112		0.112
			498.00	499.00	P003916	1.00	0.067		0.067
			499.00	500.00	P003917	1.00	0.027		0.027
			500.00	501.00	P003918	1.00	0.308		0.308
			501.00	502.00	P003919	1.00	0.099		0.099
			502.00	503.00	P003920	1.00	0.041		0.041
			503.00	504.00	P003921	1.00	0.015		0.015
			504.00	505.00	P003922	1.00	0.016		0.016
			505.00	506.00	P003923	1.00	0.023		0.023
			506.00	507.00	P003924	1.00	0.022		0.022
			507.00	508.00	P003925	1.00	0.106		0.106
			508.00	509.00	P003926	1.00	0.078		0.078
			509.00	510.00	P003928	1.00	0.134		0.134
			510.00	511.00	P003929	1.00	0.015		0.015
			511.00	512.00	P003930	1.00	1.325		1.325
512.00	513.00	P003931	1.00	0.226		0.226			
513.00	514.00	P003932	1.00	0.011		0.011			
513.70	558.00	BA; APH; MAS <b>Mafic Meta-Volcanic ; Aphanitic; Massive rock</b> Green to green-gray. Fractures filled with silica and carbonate fluid, mostly carbonate. Bands of Chlorite (1-3mm) No mineralization. Overall alteration is medium CARB, strong SI and weak CL. Talceous intervals. Strong foliation 45 TCA. Mag +. Trace of Py and Pyrrhothite to no mineralization.  E.O.H. : 558m	514.00	515.00	P003933	1.00	0.010		0.010
513.70	515.00	FAI <b>Fault 40°</b> Fault, core all broken in foliation. Fractures filled with a dark green Chlorite (70%), silica (15%) and carbonate (15%). Graphitic. Strong CL alteration.							
515.00	558.00	FOL; FRC	515.00	516.00	D953033	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
<b>Foliation 50°; Fractured</b> Strong foliation 50 TCA and fractures in foliation.			516.00	517.50	D953034	1.50	<0.005		0.001
			517.50	519.00	D953035	1.50	<0.005		0.001
			519.00	520.50	D953036	1.50	<0.005		0.001
			520.50	522.00	D953037	1.50	<0.005		0.001
			522.00	523.50	D953038	1.50	<0.005		0.001
			523.50	525.00	D953039	1.50	<0.005		0.001
			525.00	526.50	D953041	1.50	<0.005		0.001
			526.50	528.00	D953042	1.50	<0.005		0.001
			528.00	529.50	D953043	1.50	<0.005		0.001
			529.50	531.00	D953044	1.50	<0.005		0.001
			531.00	532.50	D953046	1.50	<0.005		0.001
			532.50	534.00	D953047	1.50	<0.005		0.001
			534.00	535.50	D953048	1.50	0.006		0.006
			535.50	537.00	D953049	1.50	<0.005		0.001
			537.00	538.50	D953051	1.50	<0.005		0.001
			538.50	540.00	D953052	1.50	<0.005		0.001
			540.00	541.50	D953053	1.50	<0.005		0.001
			541.50	543.00	D953054	1.50	<0.005		0.001
			543.00	544.50	D953055	1.50	0.009		0.009
			544.50	546.00	D953056	1.50	<0.005		0.001
546.00	547.50	D953057	1.50	0.005		0.005			
547.50	549.00	D953058	1.50	0.007		0.007			
549.00	550.50	D953059	1.50	0.009		0.009			
550.50	552.00	D953061	1.50	0.005		0.005			
552.00	553.50	D953062	1.50	0.007		0.007			
553.50	555.00	D953063	1.50	<0.005		0.001			
555.00	556.50	D953064	1.50	<0.005		0.001			
556.50	558.00	D953065	1.50	<0.005		0.001			
552.00	552.20	VEI;20;AbQz;T;55°;Py02; <b>Vein 20 Albite Quartz Tension 55° Pyrite02</b> albite-quartz vein	552.00	553.50	D953062	1.50	0.007		0.007
			553.50	555.00	D953063	1.50	<0.005		0.001
			555.00	556.50	D953064	1.50	<0.005		0.001
			556.50	558.00	D953065	1.50	<0.005		0.001
558.00	Fin du sondage Nombre d'échantillons : 444 Nombre d'échantillons QAQC : 49 Longueur totale échantillonnée : 554.40								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.50	15.00	D952740	D952739	1.50	<0.005	0.001
22.50	22.50	D952745	m	0.00	<0.005	0.001
30.00	30.00	D952750	O53Pb	0.00	0.631	0.631
33.20	33.20	P003786	O54Pa	0.00	2.900	2.900
45.00	46.50	D952760	D952759	1.50	0.031	0.031
61.50	61.50	D952770	O54Pa	0.00	2.900	2.900
75.00	76.50	D952780	D952779	1.50	0.007	0.007
81.00	81.00	D952785	m	0.00	<0.005	0.001
87.00	87.00	D952790	O52Pb	0.00	0.286	0.286
100.50	101.50	D952800	D952799	1.00	<0.005	0.001
116.00	116.00	D952810	O53Pb	0.00	0.599	0.599
126.00	126.00	D952817	m	0.00	<0.005	0.001
128.50	130.00	D952820	D952819	1.50	0.280	0.280
135.00	135.00	P003809	O52Pb	0.00	0.326	0.326
145.50	145.50	D952830	O54Pa	0.00	2.890	2.890
159.00	160.70	D952840	D952839	1.70	0.008	0.008
171.00	171.00	D952845	m	0.00	<0.005	0.001
177.00	177.00	D952850	O52Pb	0.00	0.298	0.298
190.50	192.00	D952860	D952859	1.50	0.014	0.014
206.00	206.00	P003832	O54Pa	0.00	2.980	2.980
229.00	229.00	D952870	O53Pb	0.00	0.590	0.590
241.50	243.00	D952880	D952879	1.50	<0.005	0.001
247.50	247.50	D952885	m	0.00	<0.005	0.001
253.50	253.50	D952890	O54Pa	0.00	2.850	2.850
267.00	268.50	D952900	D952899	1.50	<0.005	0.001
282.00	282.00	D952910	O52Pb	0.00	0.304	0.304
290.60	290.60	P003850	O53Pb	0.00	0.649	0.649
298.50	300.00	D952920	D952919	1.50	0.056	0.056
313.50	313.50	D952930	O53Pb	0.00	0.615	0.615
328.50	330.00	D952940	D952939	1.50	<0.005	0.001
334.50	334.50	D952945	m	0.00	<0.005	0.001
340.50	340.50	D952950	O54Pa	0.00	2.920	2.920
356.00	357.00	D952960	D952959	1.00	0.005	0.005

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
369.00	369.00	D952970	O52Pb	0.00	0.315	0.315
382.50	384.00	D952980	D952979	1.50	0.846	0.846
388.00	388.00	D952985	m	0.00	<0.005	0.001
396.00	396.00	D952990	O53Pb	0.00	0.646	0.646
409.50	411.00	D953000	D952999	1.50	0.235	0.235
419.60	419.60	P003873	O52Pb	0.00	0.318	0.318
430.50	430.50	D953010	O54Pa	0.00	2.640	2.640
451.50	453.00	D953020	D953019	1.50	0.133	0.133
463.00	463.00	P003886	O52Pb	0.00	0.323	0.323
468.00	468.00	D953030	O52Pb	0.00	0.311	0.311
493.00	493.00	P003911	O54Pa	0.00	2.940	2.940
508.00	508.00	P003927	O53Pb	0.00	0.666	0.666
523.50	525.00	D953040	D953039	1.50	<0.005	0.001
529.50	529.50	D953045	m	0.00	<0.005	0.001
535.50	535.50	D953050	O53Pb	0.00	0.609	0.609
549.00	550.50	D953060	D953059	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-53

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie mine

Foré par : Foramex

Lot :

Décrit par : Geneviève Carignan

Du : 2009-05-09

Date de description : 2009-05-18

Au : 2009-05-18

Collet

UTM

Azimut : 176.14°

Plongée : -55.70°

Longueur : 579.00 m

Est 630 819.3

Nord 5 374 444.9

Élévation 314.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	169.15°	-55.70°	Non
Reflex	60.00	169.45°	-55.40°	Non
Reflex	90.00	169.75°	-54.90°	Non
Reflex	120.00	169.55°	-54.60°	Non
Reflex	150.00	170.65°	-54.30°	Non
Reflex	180.00	169.65°	-53.60°	Non
Reflex	210.00	170.95°	-53.40°	Non
Reflex	240.00	171.25°	-52.90°	Non
Reflex	270.00	170.75°	-52.60°	Non
Reflex	300.00	170.45°	-51.00°	Non
Reflex	330.00	171.55°	-50.40°	Non
Reflex	360.00	172.85°	-49.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	390.00	172.45°	-49.60°	Non
Reflex	420.00	172.85°	-49.30°	Non
Reflex	450.00	171.65°	-48.80°	Non
Reflex	480.00	174.45°	-48.40°	Non
Reflex	510.00	174.25°	-48.00°	Non
Reflex	540.00	175.05°	-47.80°	Non
Reflex	570.00	175.35°	-46.90°	Non

Description

NAD 83, UTM Zone 17

(Hole surveyed (Nov 2009) by Descarreaux).

Resampled by Hillar Pintson (Original log had DDH until 600.0 m, however the hole ends at 579.0 m)

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.70	MT; LOST <b>Casing; Core Not Recovered</b> Casing  HP, 9-09-10: Interval change							
3.70	237.45	SY POR; MAG; MAS <b>Syenite Porphyry Intrusive; Magnetic; Massive rock</b> Intrusive rock. Dark purple-greyish fine to loc aphanitic matrix with 4-6% Fp phenos (0.1-1cm). Massive (with loc breccia) and magenitc. 1-2% fine Qz-Cc±Cl veins @ 40-50° TCA. Tr Smokey Qz veins @ 35° TCA. Light pervasive chloritisation and hematisation and local epidotisation (HP, sericitization, not epidotization). Weathering in the fractures until 100m. Tr-1% very fine disseminated pyrite and traces of chalcopyrite in a Qz vein. (HP, 12-09-10: 1 cm long Cpy grain in Qtz-Cc vein @ 155.3 m) 218.4-237.45m: Red syenite porphyry intrusive. Gradual contact. (HP, 12-09-10: 5-10% euhedral Fspar phenocrysts, 2-8 mm in size, scattered 1-2 cm sized phenocrysts as well)	3.70	4.90	D925762	1.20	<0.005		0.001
			4.90	6.00	D925763	1.10	<0.005		0.001
			6.00	7.50	D925764	1.50	<0.005		0.001
			7.50	9.00	D925765	1.50	<0.005		0.001
9.00	10.00	VEI;4;Qz Cc Cb;T;25°; <b>Vein 4 Quartz Calcite Carbonate Tension 25°</b> HP, 11-09-10: Five 0.5 - 4 cm wide Qtz - Cb - Cc veins @ 25 DTCA; also several veinlets; the 4 cm wide vein (Cc) is @ 40 DTCA; no Py observed	9.00	10.50	D925766	1.50	<0.005		0.001
			10.50	12.00	D925767	1.50	<0.005		0.001
12.00	14.50	VEI;2.5;Qz;T;55°; <b>Vein 2.5 Quartz Tension 55°</b> HP, 11-09-10 (12.0-12.65) Three 0.5 - 1.5 cm wide Qtz-Cb veins @ 30 DTCA; interval includes breccia with Cb matrix in (12.3-12.5); no Py observed (12.65-13.0) Badly broken core; white massive vuggy Qtz vein; some wall rock inclusions; probable upper contact @ 55 DTCA; no Py observed (13.0-14.0) Syenite (14.0-14.2) Badly broken core; white massive Qtz vein; no Py observed (14.2-14.4) Syenite (14.4-14.5) Badly broken core; white massove Qtz vein; no Py observed	12.00	13.50	D925768	1.50	<0.005		0.001
12.30	12.50	BRE							



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Breccia 60°</b> Breccia. Siliceous syenite fragments in a chlorite-carbonates matrix.						
12.50	14.50	FRC	13.50	15.00	D925770	1.50	<0.005	0.001
		<b>Fractured</b> 80% broken core.	15.00	16.50	D925771	1.50	<0.005	0.001
			16.50	18.00	D925772	1.50	<0.005	0.001
			18.00	19.50	D925773	1.50	<0.005	0.001
18.70	19.15	VEI;15;QzCl;;; <b>Vein 15 Quartz Chlorite</b> White Qz-Ch injection.	19.50	21.00	D925774	1.50	0.006	0.006
			21.00	22.50	D925775	1.50	0.020	0.020
			22.50	24.00	D925776	1.50	<0.005	0.001
		HP, 11-09-10: Interval change to (18.7-19.15) from (18.9-19.1); irregular Qtz-Cc-Cb-Chl vein @ 10 DTCA; no Py observed	24.00	25.50	D925777	1.50	<0.005	0.001
			25.50	27.00	D925778	1.50	<0.005	0.001
			27.00	28.50	D925780	1.50	<0.005	0.001
			28.50	29.70	D925781	1.20	<0.005	0.001
29.50	31.30	Hem <b>Hematization</b> Light hematization and chloritisation overlaid by weathering.						
29.70	31.20	FRC; FOL	29.70	31.20	D925782	1.50	0.384	0.384
		<b>Fractured 65°; Foliation</b> HP, 11-09-10: Fracture - shear zone; abundant mm-spaced fractures; fractures in upper part of interval @ 65 DTCA; fractures - foliation @ 35 DTCA in lower part of interval; carbonatized (Cb and Cc) - silicified - pink Fspar (may occur as up to 6 cm wide veins or injection zones); some Sericite; trace disseminated Py locally; gradational upper and lower contacts	31.20	32.70	D925783	1.50	0.071	0.071
			32.70	33.60	D925784	0.90	0.005	0.005
32.80	33.30	FOL; FRC <b>Foliation 65°; Fractured</b> HP, 11-09-10: Shear - fracture zone; mostly sericitized, also chloritized - carbonatized (Cb); foliation defined by mm spaced Ser-coated fractures @ 65 DTCA; gradational upper contact; lower contact marked by a 6 cm wide vuggy Qtz - Cc - Cb vein @ 70 DTCA; no Py observed	33.60	35.30	D925785	1.70	<0.005	0.001
35.30	39.50	FOL <b>Foliation 65°</b> HP, 11-09-10: Foliation @ 65 DTCA defined by cm spaced Ser-, lesser Chl, coated fractures	35.30	36.50	D925786	1.20	<0.005	0.001
			36.50	38.00	D925787	1.50	<0.005	0.001
			38.00	39.50	D925788	1.50	0.011	0.011
			39.50	41.00	D925790	1.50	0.005	0.005
			41.00	42.50	D925791	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
42.50	44.20	FOL; CIS <b>Foliation 85°; Sheared</b> HP, 11-09-10: Shear - alteration zone; weakly to well developed foliation @ 85 DTCA; best developed foliation and parallel alignment of completely chloritized Fspar phenocrysts in (43.3-43.8); foliation in lower part of interval @ 50 DTCA; mostly sericitized, also chloritized and carbonatized (Cb); scattered slightly cross cutting to cross cutting up to 2 cm wide Qtz - Cb - Cc veinlets - veins; rare disseminated Py in wall rock and in veinlets - veins; gradational contacts	42.50	44.20	D925792	1.70	0.047		0.047
42.60	44.20	Epi; Chl <b>Epidotisation; Chloritisation</b> Light pervasive epidotisation (HP, sericitization, not epidotization) and chloritisation.	44.20	45.50	D925793	1.30	0.012		0.012
			45.50	46.90	D925794	1.40	0.007		0.007
			46.90	48.20	D925796	1.30	<0.005		0.001
48.20	49.70	Epi; Chl <b>Epidotisation; Chloritisation</b> Light pervasive epidotisation (HP, sericitization, not epidotization) and chloritisation.							
48.20	49.70	FOL; CIS <b>Foliation 60°; Sheared</b> HP, 11-09-10: Shear - alteration zone; mostly sericitized, also chloritized; weakly to well developed foliation; best developed foliation in (48.7-49.2) @ 60 DTCA with 25% Qtz - Cc - Cb veinlets and one 3 cm wide Qtz vein; trace disseminated Py in wall rock and in veinlets, 1% disseminated up to 1 mm sized Py cubes over a few cm at 48.43 m; gradational upper contact; diffuse lower contact marked by rather abrupt end of sericitization @ 40 DTCA	48.20	49.70	D925797	1.50	0.061		0.061
			49.70	51.20	D925798	1.50	<0.005		0.001
			51.20	52.60	D925800	1.40	0.030		0.030
			52.60	54.00	D925801	1.40	0.140		0.140
			54.00	55.00	P003535	1.00	0.039		0.039
54.30	56.20	Epi; Chl <b>Epidotisation; Chloritisation</b> Light to moderate pervasive epidotisation (HP, sericitization, not epidotization) and chloritisation.							
54.30	56.70	FOL; CIS <b>Foliation 55°; Sheared</b> HP, 11-09-10: Shear - alteration zone; moderately developed foliation - mm wide laminations @ 55 DTCA; mostly sericitized, also chloritized; 75% 0.5 - 13 cm wide Qtz, minor Cb, veins in (54.9-55.35), essentially foliation parallel with trace to 1% disseminated Py; trace to 1% disseminated Py in wall rock as well; gradational contacts	55.00	56.00	P003536	1.00	0.404		0.404
			56.00	57.00	P003537	1.00	0.145		0.145

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
54.30	56.20	Py01 <b>Pyrite 01%</b> Tr-1% very fine to fine disseminated pyrite.						
56.20	61.70	Hem <b>Hematisation</b> Light pervasive hematisation.	57.00	58.50	D925802	1.50	0.025	0.025
			58.50	60.00	D925803	1.50	0.050	0.050
			60.00	61.70	D925804	1.70	0.033	0.033
61.70	63.40	STW;20%;Qz Cb;T;45°;Py00; <b>Stockwerk 20% Quartz Carbonate Tension 45° Pyrite 0.01%</b> HP, 11-09-10: 20% regular to irregular Qtz - Cb veinlets - up to 2 cm wide veins and cm-sized aggregates; mostly @ 45 DTCA; rare Py	61.70	63.40	D925805	1.70	0.120	0.120
			63.40	64.50	D925806	1.10	0.119	0.119
			64.50	66.00	D925807	1.50	<0.005	0.001
			66.00	67.50	D925808	1.50	0.119	0.119
			67.50	69.00	D925810	1.50	<0.005	0.001
			69.00	70.50	D925811	1.50	<0.005	0.001
			70.50	72.00	D925812	1.50	0.006	0.006
72.00	74.00	FRC <b>Fractured 45°</b> HP, 11-09-10: Fracture zone; pseudo-foliation - alignment of mm-spaced Ser-Chl - coated fractures @ 45 DTCA; gradational contacts	72.00	73.00	P003538	1.00	0.189	0.189
72.10	72.50	Py02 <b>Pyrite 02%</b> 1-2% very fine disseminated pyrite.	73.00	74.00	P003540	1.00	0.005	0.005
			74.00	75.00	D925813	1.00	<0.005	0.001
			75.00	76.50	D925814	1.50	<0.005	0.001
			76.50	78.00	D925815	1.50	0.007	0.007
			78.00	79.50	D925816	1.50	<0.005	0.001
			79.50	81.00	D925817	1.50	<0.005	0.001
81.00	115.50	FRC; FOL <b>Fractured 45°; Foliation</b> HP, 11-09-10: 75% dm-m scale intervals with weakly developed foliation (alignment of Ser-Chl - coated fractures) and dm scale intervals with moderately to well developed foliation; foliation @ 30-50 DTCA; best developed foliation in (83.7-84.6), (90.9-92.4), (97.5-101.8), these intervals also have associated Qtz veinlets - veins - silicification; gradational contacts between different degrees of foliation development and for the interval as a whole	81.00	82.00	D925818	1.00	<0.005	0.001
			82.00	83.00	D925820	1.00	<0.005	0.001
			83.00	84.00	P003541	1.00	0.639	0.639
83.60	84.40	Py02 <b>Pyrite 02%</b> 1-2% very fine disseminated pyrite.	84.00	85.00	P003542	1.00	0.716	0.716
			85.00	86.50	204952	1.50	0.010	0.010
			86.50	88.00	204953	1.50	0.030	0.030

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			88.00	89.00	204954	1.00	0.006		0.006
			89.00	90.00	204955	1.00	0.049		0.049
			90.00	91.00	P003543	1.00	0.183		0.183
90.10	90.30	Py02 <b>Pyrite 02%</b> 2% very fine disseminated pyrite.							
91.00	106.70	Py03 <b>Pyrite 03%</b> 2-3% very fine disseminated pyrite associated with 1cm thick smokey Qz veins and siliceous breccia.	91.00	92.00	P003544	1.00	1.675		1.675
			92.00	93.00	P003545	1.00	0.417		0.417
			93.00	94.00	P003546	1.00	0.418		0.418
			94.00	95.00	P003547	1.00	0.387		0.387
		HP, 11-09-10: Also minor Cb and Cc; sample intervals with the best assay values also contain Py stringers parallel to veinlet - vein margins or parallel to foliation	95.00	96.00	P003548	1.00	0.921		0.921
			96.00	97.00	P003549	1.00	0.577		0.577
			97.00	98.00	P003550	1.00	0.335		0.335
97.50	100.00	Epi; Ser <b>Epidotisation; Sericitisation</b> Light epidotisation (HP, sericitization, not epidotization) and sericitisation. (HP, also lesser chloritization)	98.00	99.00	P003551	1.00	0.507		0.507
			99.00	100.00	P003552	1.00	0.701		0.701
			100.00	101.00	P003553	1.00	1.165		1.165
			101.00	102.00	P003554	1.00	0.560		0.560
			102.00	103.00	P003555	1.00	0.486		0.486
			103.00	104.00	P003557	1.00	0.079		0.079
			104.00	105.00	P003558	1.00	0.120		0.120
			105.00	106.00	P003559	1.00	0.515		0.515
			106.00	107.00	P003560	1.00	1.390		1.390
			107.00	108.00	P003561	1.00	0.060		0.060
			108.00	109.50	204956	1.50	<0.005		0.001
			109.50	111.00	204957	1.50	0.005		0.005
			111.00	112.50	204958	1.50	0.005		0.005
			112.50	114.00	204959	1.50	0.007		0.007
			114.00	115.40	204960	1.40	0.006		0.006
			115.40	117.00	204962	1.60	0.006		0.006
			117.00	118.50	204963	1.50	0.005		0.005
			118.50	120.00	204964	1.50	<0.005		0.001
			120.00	121.50	204965	1.50	0.005		0.005
			121.50	123.00	204966	1.50	<0.005		0.001
			123.00	124.50	204967	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			124.50	126.00	204968	1.50		0.023	
			126.00	127.00	P003562	1.00		0.138	0.138
127.00	127.50	Sil <b>Silicification</b> Light pervasive silicification.							
127.00	129.00	FOL; CIS <b>Foliation 45°; Sheared</b> HP, 11-09-10: Shear zone; well developed foliation @ 45 DTCA; strongly sericitized; trace disseminated Py; a few barren cross cutting to foliation parallel 0.5 - 3 cm wide Qtz, minor Cb, veins; upper contact marked by a silicified zone; lower gradational contact	127.00	128.00	P003563	1.00		0.317	0.317
127.00	127.50	Py02 <b>Pyrite 02%</b> 1-3% very fine disseminated pyrite in a siliceous syenite.							
127.50	128.70	Chl; Ser <b>Chloritisation; Sericitisation</b> Moderate chloritisation with light sericitisation. Making a foliation @ 55° TCA.	128.00	129.00	P003564	1.00		0.021	0.021
			129.00	130.50	D925821	1.50		0.009	0.009
			130.50	132.00	D925822	1.50		0.012	0.012
131.00	133.20	Chl; Ser; Epi <b>Chloritisation; Sericitisation; Epidotisation</b> Moderate chloritisation and light sericitisation and epidotisation (HP, sericitization, not epidotization) making a foliation @ 55-60° TCA.							
131.00	133.80	FOL; CIS <b>Foliation 60°; Sheared</b> HP, 11-09-10: Shear zone; moderately to well developed foliation; best developed foliation @ 60 DTCA in (131.5-133.7); strongly sericitized, also chloritized and slightly carbonatized (Cb); trace disseminated Py; foliation parallel to cross cutting 0.5 - 4 cm wide Qtz, minor Cb, veins scattered throughout interval, locally with trace to 1% disseminated Py	132.00	133.00	P003565	1.00		0.020	0.020
			133.00	134.00	P003566	1.00		1.055	1.055
133.20	135.70	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Intrusive rock. Dark purple- grey aphanitic matrix with 15% Fp lath phenos (0.3-1cm) aligned @ 50-60° TCA. Massive and non magnetic. Trachytic texture. Tr white Qz-Cc injections. Light pervasive chloritisation and albitisation? 1% very fine disseminated pyrite.	134.00	135.00	P003567	1.00		1.135	1.135
			135.00	136.00	P003568	1.00		0.101	0.101

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
135.90	144.00	Upper contact sharp @ 45° TCA, lower @ 55° TCA.  FOL <b>Foliation 65°</b> HP, 11-09-10: Moderately developed foliation @ 65 DTCA defined by parallel alignment of mm spaced sericitized - chloritized fractures; gradational contacts	136.00	137.00	P003569	1.00	0.041		0.041
			137.00	138.00	P003570	1.00	0.006		0.006
			138.00	139.50	D925823	1.50	0.014		0.014
			139.50	141.00	D925824	1.50	<0.005		0.001
			141.00	142.50	D925825	1.50	0.032		0.032
			142.50	144.00	D925826	1.50	0.029		0.029
			144.00	145.50	D925827	1.50	0.013		0.013
			145.50	147.00	D925828	1.50	0.069		0.069
			147.00	148.50	D925830	1.50	0.018		0.018
			148.50	150.00	D925831	1.50	0.011		0.011
			150.00	151.50	D925832	1.50	<0.005		0.001
			151.50	153.00	D925833	1.50	<0.005		0.001
			153.00	154.50	D925834	1.50	0.005		0.005
			154.50	156.00	D925836	1.50	0.013		0.013
			156.00	157.50	D925837	1.50	0.005		0.005
157.50	159.00	D925838	1.50	0.491		0.491			
158.40	178.20	Chl; Epi; Ser <b>Chloritisation; Epidotisation; Sericitisation</b> Moderate chloritisation and light sericitisation and epidotisation (HP, sericitization, not epidotization).							
158.50	165.00	FOL; CIS <b>Foliation 30°; Sheared</b> HP, 12-09-10: Shear zone; moderately to well developed foliation; gradational contact zones with mm spaced Ser-Chl - coated fractures; best developed foliation in (160.0-164.0), strongly sericitized and chloritized; 80% foliation parallel to cross cutting, essentially barren, Qtz-Cb veinlets - veins in (162.55-163.5) with up to 1% disseminated Py in wall rock slivers; locally up to 1% disseminated Py in foliated wall rock as well							
159.00	162.50	Py03 <b>Pyrite 03%</b> 2-3% fine to loc cubic disseminated pyrite.	159.00	160.00	P003571	1.00	0.035		0.035
			160.00	161.00	P003572	1.00	0.087		0.087
			161.00	162.00	P003573	1.00	0.070		0.070
			162.00	163.10	P003574	1.10	1.265		1.265

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
162.50	163.20	VEI;70;QzFp;;;Py0.5; <b>Vein 70 Quartz Feldspath (alkaline) Pyrite0.5%</b> Zone of Qz-Fp injections with traces of pyrite.	163.10	164.10	P003575	1.00	0.023		0.023
			164.10	165.00	D925840	0.90	0.014		0.014
			165.00	166.50	D925841	1.50	0.021		0.021
			166.50	168.00	D925842	1.50	<0.005		0.001
			168.00	169.50	D925843	1.50	<0.005		0.001
168.70	169.40	VEI;1;Qz Cb;T;;; <b>Vein 1 Quartz Carbonate Tension</b> HP, 12-09-10: 1 cm wide Qtz, minor Cb, vein @ 10 DTCA, barren; trace to 0.2% fine disseminated Py in wall rock	169.50	171.00	D925844	1.50	<0.005		0.001
			171.00	172.50	D925845	1.50	<0.005		0.001
			172.50	174.00	D925846	1.50	<0.005		0.001
			174.00	175.50	D925847	1.50	<0.005		0.001
175.00	177.70	FOL <b>Foliation 40°</b> HP, 12-09-10: Foliated alteration zone; weakly - moderately developed foliation @ 40 DTCA defined by parallel alignment of Ser-Chl - coated fractures and mm-cm wide Ser-rich shear bands; moderately sericitized - chloritized; rare Py; gradational contacts	175.50	177.00	D925848	1.50	<0.005		0.001
			177.00	178.20	D925850	1.20	<0.005		0.001
178.20	179.90	Car; Sil <b>Carbonatation; Silicification</b> HP, 12-09-10: Moderate carbonatization (Cc) and silicification (Qtz veinlets - flooding); also hematitization, sericitization and chloritization	178.20	179.90	D925851	1.70	<0.005		0.001
			179.90	181.50	D925852	1.60	0.075		0.075
180.20	182.00	FOL <b>Foliation 40°</b> HP, 12-09-10: Moderately developed foliation @ 40 DTCA defined by mm-cm spaced Ser-Chl - coated fractures; sericitized wall rock; trace to 0.2% disseminated Py; up to 1% disseminated Py over a few cm adjacent to a 2 cm wide barren Qtz - Cb vein; gradational contacts for the interval	181.50	183.00	D925853	1.50	<0.005		0.001
			183.00	184.50	D925854	1.50	<0.005		0.001
			184.50	186.00	D925855	1.50	<0.005		0.001
			186.00	187.50	D925856	1.50	<0.005		0.001
			187.50	189.00	D925857	1.50	<0.005		0.001
			189.00	190.50	D925858	1.50	<0.005		0.001
			190.50	192.00	D925860	1.50	<0.005		0.001
			192.00	193.50	D925861	1.50	<0.005		0.001
			193.50	195.00	D925862	1.50	0.065		0.065
			195.00	196.00	D925863	1.00	<0.005		0.001
			196.00	197.00	D925864	1.00	<0.005		0.001
197.90	198.20	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite in a siliceous-carbonates	197.00	198.00	P003576	1.00	0.051		0.051
			198.00	199.00	P003577	1.00	0.648		0.648
			199.00	200.00	P003578	1.00	0.073		0.073

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		breccia. Contacts sharp @ 50-60° TCA.	200.00	201.00	P003579	1.00	0.833		0.833
200.75	201.25	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite in a siliceous-carbonates breccia crosscut by Smokey Qz veins @ 45-50° TCA. Contacts sharp @ 40-50° TCA.	201.00	202.00	P003580	1.00	1.290		1.290
			202.00	203.00	P003581	1.00	0.088		0.088
			203.00	204.00	P003583	1.00	0.044		0.044
			204.00	205.00	P003584	1.00	0.014		0.014
			205.00	206.00	P003585	1.00	0.105		0.105
			206.00	207.00	P003586	1.00	0.073		0.073
206.60	206.70	Py02 <b>Pyrite 02%</b> 1-2% very fine disseminated pyrite in a siliceous-carbonates vein @ 30° TCA.  HP 12-09-10: 4 cm wide Cc - Qtz vein	207.00	208.00	P003587	1.00	0.142		0.142
			208.00	209.00	D925865	1.00	0.527		0.527
			209.00	210.00	D925866	1.00	0.667		0.667
			210.00	211.50	D925867	1.50	0.005		0.005
			211.50	213.00	D925868	1.50	0.022		0.022
			213.00	214.50	D925870	1.50	0.011		0.011
			214.50	216.00	D925871	1.50	0.048		0.048
			216.00	217.50	D925872	1.50	0.149		0.149
			217.50	219.00	D925873	1.50	0.023		0.023
			219.00	220.50	D925874	1.50	0.052		0.052
			220.50	222.00	D925876	1.50	0.043		0.043
			222.00	223.50	D925877	1.50	0.007		0.007
			223.50	225.00	D925878	1.50	0.025		0.025
			225.00	226.50	D925880	1.50	0.025		0.025
			226.50	228.00	D925881	1.50	0.087		0.087
			228.00	228.90	D925882	0.90	0.080		0.080
			228.90	230.00	P003588	1.10	0.030		0.030
			230.00	231.00	P003589	1.00	0.541		0.541
230.20	230.65	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite associated with a 3cm Qz-Cc vein @ 40-50° TCA.	231.00	232.00	P003590	1.00	0.323		0.323
			232.00	233.00	D925883	1.00	0.066		0.066
			233.00	234.00	D925884	1.00	0.183		0.183
			234.00	235.50	D925885	1.50	0.140		0.140
			235.50	237.00	D925886	1.50	0.116		0.116
			237.00	238.00	P003591	1.00	0.808		0.808
237.45	242.00	SY; FOL; CIS <b>Syenite 50°; Foliation ; Sheared</b>							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
237.45	313.10	<p>Intrusive rock. Maybe an altered syenite. Grey-green fine grained matrix. Foliation @ 50° TCA. Massive and magnetic.</p> <p>Tr Smokey Qz veins @ 40° TCA.</p> <p>Light to moderate chloritisation and light sericitisation.</p> <p>1-2% very fine disseminated pyrite associated with smokey Qz veins.</p> <p>Sharp contacts @ 50° TCA.</p> <p>HP, 12-09-10: Foliated Syenite; very well developed foliation @ 50 DTCA; sharp upper contact marked by a Qtz-Cb veinlet @ 55 DTCA; fairly sharp slightly irregular lower contact @ 50 DTCA; 7 cm wide brecciated silicified zone - Qtz veining-flooding interval with 5-10% Py stringers - fracture fill @ 40 DTCA at 238.15 m</p> <p>FOL; CIS</p> <p><b>Foliation 40°; Sheared</b></p> <p>Mega Shear Zone (individual intervals described in Litho 1)</p> <p>(269.8-270.1) HP, 12-09-10: Fault; powdery, flakey and foliated; sharp upper contact @ 20 DTCA, sharp lower contact @ 15 DTCA; cross cuts 25-30 DTCA foliation in wall rock</p> <p>(279.9-280.8) Breccia. Purple and beige (bleached) syenite fragments in a sericite matrix. 1-2% very fine pyrite. Contacts (HP, and foliation in overlying wall rock) @ 20° TCA.</p>	238.00	239.00	P003592	1.00	0.709		0.709
			239.00	240.00	P003593	1.00	0.034		0.034
			240.00	241.00	P003594	1.00	0.090		0.090
			241.00	242.00	P003595	1.00	0.015		0.015
242.00	249.00	<p>SY; BSF</p> <p><b>Syenite; Breccia Silicified zone</b></p> <p>Mineralized zone. Brecciated, siliceous-carbonates mineralized syenite.</p> <p>Light albitisation?</p> <p>3-5% very fine disseminated pyrite.</p> <p>Sharp contact @ 50° TCA.</p> <p>HP, 12-09-10: Silicified breccia zone in Syenite in (242.0-245.0); also carbonatized (Cb and minor Cc); (245.0-249.0) consists of silicified brecciated - fractured Syenite with gradual decrease in amount of brecciation and silicification and re-appearance of foliation in lower 1 m of interval, interval also contains trace disseminated Aspy locally</p>	242.00	243.00	P003596	1.00	4.560	4.97	4.970
			243.00	243.90	P003597	0.90	4.000	4.28	4.280
			243.90	244.90	P003598	1.00	3.620	4.03	4.030
			244.90	246.00	P003599	1.10	3.260	3.41	3.410
			246.00	247.00	P003601	1.00	4.090	4.54	4.540
			247.00	248.00	P003602	1.00	1.750		1.750
			248.00	249.00	P003603	1.00	0.788		0.788
249.00	251.20	<p>SY; FOL</p> <p><b>Syenite 40°; Foliation</b></p> <p>Altered syenite. Pale green-greyish fine grained to aphanitic matrix.</p> <p>Lower contact of the mineralized zone.</p> <p>1% smokey Qz veins @ 20-40° TCA.</p> <p>Light chloritisation.</p>	249.00	250.00	P003604	1.00	0.347		0.347

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
Contacts are gradual.								
HP, 12-09-10: Chloritized, sericitized and carbonatized (Cb); fairly well developed foliation @ 40 DTCA								
249.90	250.70	Py03	250.00	251.00	P003605	1.00	2.230	2.230
		<b>Pyrite 03%</b>	251.00	252.00	P003606	1.00	0.486	0.486
		2-3% very fine disseminated pyrite in a siliceous lightly brecciated syenite.						
251.20	261.60	SY; FOL	252.00	253.50	204969	1.50	0.007	0.007
		<b>Diorite 50°; Foliation</b>	253.50	255.00	204970	1.50	<0.005	0.001
		Intrusive rock. Dark green to pale green fine grained matrix. Massive (HP, well foliated), homogenous and magnetic.	255.00	256.50	D925887	1.50	0.005	0.005
		1% Cc veins @ 50° TCA	256.50	258.00	D925888	1.50	<0.005	0.001
		Light (HP, strong) chloritisation.	258.00	259.60	D925890	1.60	<0.005	0.001
		Tr-1% very fine to fine disseminated pyrite.	259.60	261.00	204973	1.40	0.014	0.014
		Upper contact is gradual and lower contact @ 45° TCA.	261.00	262.50	204971	1.50	1.520	1.520
HP, 12-09-10: Well foliated mafic intrusive (diorite?); foliation @ 50 DTCA; strongly chloritized								
261.60	313.10	SY; FOL						
		<b>Syenite 40°; Foliation</b>						
		Intrusive rock. Bleached and chloritized syenite. Pale green-beige to dark green aphanitic to fine grained matrix. Heterogenous, foliated @ 40° TCA and magnetic. Locally brecciated.						
		Moderate bleaching and chloritisation with light sericitisation.						
		Alternating zones of bleaching and chloritisation with sericitisation everywhere.						
		Tr very fine to fine disseminated pyrite.						
		Lower contact sharp @ 50° TCA.						
HP, 12-09-10: Well developed foliation @ 40 DTCA, locally @ 30 DTCA; trace Aspy locally as well								
(270.9-274.4) Medium- dark purplish green; chloritized; strongly magnetic								
(277.4-279.0) Brecciated - breccia								
262.00	265.70	Py03	262.50	264.00	204972	1.50	2.550	2.550
		<b>Pyrite 03%</b>	264.00	265.00	P003607	1.00	1.995	1.995
		(265.35-265.7) 2-3% very fine disseminated pyrite in a siliceous-carbonates breccia.	265.00	266.00	P003608	1.00	2.780	2.780
			266.00	267.00	P003609	1.00	0.009	0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
HP, 12-09-10: Interval change from (265.35-265.7) to (262.0-265.7); local cm-dm scale silicified zones with up to 1% fine disseminated Py as well	267.00	268.50	D925891	1.50	0.017		0.017
	268.50	269.80	D925892	1.30	0.021		0.021
	269.80	270.90	D925893	1.10	<0.005		0.001
	270.90	272.60	D925894	1.70	0.007		0.007
	272.60	274.30	D925895	1.70	<0.005		0.001
	274.30	276.00	D925896	1.70	<0.005		0.001
	276.00	277.40	D925897	1.40	0.005		0.005
	277.40	279.00	D925898	1.60	0.015		0.015
	279.00	280.00	P003610	1.00	0.028		0.028
	280.00	281.00	P003611	1.00	0.016		0.016
	281.00	282.00	228847	1.00	0.008		0.008
	282.00	283.50	D925900	1.50	0.010		0.010
	283.50	285.00	D925901	1.50	<0.005		0.001
	285.00	286.50	D925902	1.50	<0.005		0.001
	286.50	288.00	D925903	1.50	<0.005		0.001
	288.00	289.50	D925904	1.50	0.008		0.008
	289.50	291.00	D925905	1.50	0.009		0.009
	291.00	292.50	D925906	1.50	<0.005		0.001
	292.50	294.00	D925907	1.50	<0.005		0.001
	294.00	295.50	D925908	1.50	<0.005		0.001
	295.50	297.00	D925910	1.50	0.271		0.271
	297.00	298.50	D925911	1.50	<0.005		0.001
	298.50	300.00	D925912	1.50	0.011		0.011
	300.00	301.50	D925913	1.50	<0.005		0.001
	301.50	303.00	D925914	1.50	<0.005		0.001
	303.00	304.50	D925916	1.50	<0.005		0.001
	304.50	306.00	D925917	1.50	<0.005		0.001
	306.00	307.50	D925918	1.50	0.421		0.421
	307.50	309.00	D925920	1.50	0.040		0.040
	309.00	310.50	D925921	1.50	0.063		0.063
310.50	312.00	204974	1.50	1.105		1.105	
312.00	313.50	204975	1.50	0.157		0.157	
313.50	315.00	204976	1.50	0.334		0.334	
313.10	388.50	SY Syenite					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Intrusive rock. Purple greenish aphanitic matrix with 1-2% (loc4%) Fp phenos (0.1-0.5cm). Massive (loc foliation @ 40°TCA) and magnetic. Loc brecciated. Tr Qz±Cc veins @ 30° TCA. Light chloritisation (dark green stringers and pale foliation) and sericitisation (foliation). Tr-1% very fine disseminated pyrite and traces of chalcopyrite in a Qz vein. Upper contact @ 50° TCA.			315.00	316.00	204977	1.00	0.389		0.389
			316.00	317.00	204978	1.00	0.310		0.310
			317.00	318.00	228849	1.00	0.417		0.417
HP, 13-09-10: (310.5-329.0) Scattered cm-dm scale silicified zones or zones with Qtz-Cb veinlets often with fine Py disseminations and with Py stringers; in (313.1-329.0) Syenite contains mm-cm spaced mm wide parallel Ser-rich fractures @ 40 DTCA (pseudo-foliation), silicified zones - Qtz veinlets are generally parallel to these fractures (353.0-388.5) Fine disseminated Py; Py associated with weakly silicified zones; Py as fracture fill Gradational lower contact									
317.90	318.30	Py02	318.00	319.00	228850	1.00	0.650		0.650
		<b>Pyrite 02%</b>	319.00	320.00	228851	1.00	0.150		0.150
		2-3% very fine disseminated pyrite.	320.00	321.50	204979	1.50	0.222		0.222
			321.50	323.00	204980	1.50	0.229		0.229
			323.00	324.50	204982	1.50	0.285		0.285
			324.50	326.00	204983	1.50	0.545		0.545
			326.00	327.00	228852	1.00	0.386		0.386
326.70	327.20	Py02	327.00	328.00	228853	1.00	0.591		0.591
		<b>Pyrite 02%</b>	328.00	329.00	228854	1.00	1.675		1.675
		1-2% very fine disseminated pyrite.	329.00	330.00	228855	1.00	0.037		0.037
			330.00	331.00	228856	1.00	0.037		0.037
			331.00	332.00	P003612	1.00	0.017		0.017
			332.00	333.00	P003613	1.00	0.017		0.017
			333.00	334.00	P003614	1.00	0.052		0.052
			334.00	335.00	P003615	1.00	0.005		0.005
			335.00	336.00	P003616	1.00	0.013		0.013
			336.00	337.00	P003617	1.00	0.005		0.005
			337.00	338.10	P003618	1.10	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
339.35	339.45	Py05 <b>Pyrite 05%</b> 4-6% very fine disseminated pyrite in a siliceous syenite.	338.10	339.00	P003619	0.90	0.115		0.115
			339.00	340.00	P003620	1.00	0.204		0.204
			340.00	341.00	P003621	1.00	<0.005		0.001
			341.00	342.00	D925922	1.00	0.021		0.021
341.70	360.50	FRC; BC <b>Fractured ; Broken core</b> 80% broken core.  HP, 13-09-10: Interval is (339.2-339.33); only 0.5% disseminated Py	342.00	343.50	D925923	1.50	0.012		0.012
			343.50	345.00	D925924	1.50	0.006		0.006
			345.00	346.50	D925925	1.50	0.005		0.005
			346.50	348.00	D925926	1.50	0.450		0.450
			348.00	349.50	D925927	1.50	2.060		2.060
			349.50	351.00	D925928	1.50	<0.005		0.001
			351.00	352.00	D925930	1.00	<0.005		0.001
			352.00	353.00	P003622	1.00	0.008		0.008
353.00	354.20	Py04 <b>Pyrite 04%</b> 2-4% very fine disseminated pyrite. (HP, fracture fill)	353.00	354.00	P003623	1.00	2.640		2.640
			354.00	355.00	P003624	1.00	0.478		0.478
			355.00	356.00	P003625	1.00	0.031		0.031
			356.00	357.00	P003627	1.00	0.009		0.009
			357.00	358.00	P003628	1.00	0.794		0.794
357.20	357.60	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite in a siliceous syenite.	358.00	359.00	P003629	1.00	0.006		0.006
			359.00	360.00	P003630	1.00	0.373		0.373
			360.00	361.00	P003631	1.00	0.159		0.159
360.50	397.50	FRC <b>Fractured</b> HP, 13-09-10: Abundant Chl-coated fractures and veinlets mostly @ 0-30 DTCA; local dm scale brecciated zones with Chl-rich matrix; competent core	361.00	362.00	P003632	1.00	0.042		0.042
			362.00	363.00	P003633	1.00	1.010		1.010
			363.00	364.00	P003634	1.00	0.356		0.356
			364.00	365.00	P003635	1.00	1.495		1.495
			365.00	366.00	P003636	1.00	1.945		1.945
			366.00	367.00	P003637	1.00	2.340		2.340
366.60	368.20	Sil <b>Silicification</b> Moderate to high pervasive silicification.							
366.60	368.20	Py04 <b>Pyrite 04%</b>	367.00	368.00	P003638	1.00	7.010	7.20	7.200

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
3-5% very fine disseminated pyrite in a siliceous matrix.			368.00	369.00	P003639	1.00	6.210	6.90	6.900
			369.00	370.00	P003640	1.00	3.240	3.51	3.510
			370.00	371.00	P003641	1.00	0.846		0.846
			371.00	372.00	P003642	1.00	0.928		0.928
			372.00	373.00	P003643	1.00	0.792		0.792
			373.00	374.00	P003644	1.00	1.660		1.660
			374.00	375.00	P003645	1.00	0.959		0.959
			375.00	376.00	P003646	1.00	2.770		2.770
			376.00	376.90	P003647	0.90	1.305		1.305
			376.90	378.00	P011197	1.10	1.150		1.150
			378.00	379.10	P011198	1.10	0.469		0.469
			379.10	380.50	204984	1.40	1.080		1.080
			380.50	382.00	204985	1.50	0.956		0.956
			382.00	383.50	204986	1.50	0.198		0.198
			383.50	385.00	204987	1.50	0.305		0.305
			385.00	386.00	204988	1.00	0.551		0.551
			386.00	387.00	P011199	1.00	0.872		0.872
			387.00	388.00	P011200	1.00	2.330		2.330
			388.00	389.00	P011201	1.00	2.050		2.050
			388.50	398.50	Qz	389.00	390.00	P011202	1.00
		<b>Quartz</b>	390.00	391.00	P011203	1.00	2.390	2.390	
		Mineralized zone. Brecciated, siliceous-carbonates mineralized	391.00	392.00	P011204	1.00	2.640	2.640	
		syenite. Still see the Fp phenos.	392.00	393.00	P011205	1.00	1.760	1.760	
		tr-1% Smokey Qz veins @ 55° TCA.	393.00	394.00	P011206	1.00	2.080	2.080	
		Light epidotisation and albitisation?	394.00	395.00	P011207	1.00	1.455	1.455	
		3-5% very fine disseminated pyrite.	395.00	396.00	P011208	1.00	1.615	1.615	
		Sharp contact but irregular.	396.00	397.00	P011209	1.00	1.770	1.770	
		HP, 13-09-10: (397.5-398.5) Breccia; Cb matrix	397.00	398.00	P011210	1.00	1.825	1.825	
			398.00	399.00	P011211	1.00	0.732	0.732	
397.50	400.00	BRE							
		<b>Breccia</b>							
		HP, 13-09-10: Syenite breccia; Cb matrix							
398.50	513.70	SY	399.00	400.00	P011212	1.00	0.008	0.008	
		<b>Syenite</b>	400.00	401.00	204989	1.00	0.010	0.010	
		Intrusive rock. Purple-grey-greenish matrix. Massive and magnetic.	401.00	402.00	204990	1.00	0.007	0.007	

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		Loc brecciated. Traces of specular hematite in veinlets.	402.00	403.50	204991	1.50		0.008
		From 507 to 513.7m the syenite is dark green, massive.	403.50	405.00	204992	1.50		0.006
		Tr-1% Qz-Cc veins @ 50° TCA.	405.00	406.00	P011214	1.00		0.028
		Light chloritisation in dark green stringers.						
		Tr-1% (loc 2%) very fine disseminated pyrite.						
		Upper contact sharp but irregular.						
		HP, 14-09-10: Fairly regular gradational contact @ 45 DTCA						
405.90	407.10	Sil; Epi						
		<b>Silicification; Epidotisation</b>						
		Light silicification and epidotisation. (HP, Sericitization, not epidotization)						
405.90	407.10	Py02	406.00	407.00	P011215	1.00		0.642
		<b>Pyrite 02%</b>	407.00	408.00	P011216	1.00		0.286
		1-2% very fine disseminated pyrite.	408.00	409.00	P011217	1.00		0.123
		No sharp contacts.	409.00	410.00	P011218	1.00		0.190
		HP, 13-09-10: Some silicification and Cb carbonatization	410.00	411.50	204993	1.50		0.075
			411.50	413.00	204994	1.50		0.152
			413.00	414.50	204995	1.50		0.031
			414.50	415.70	D925931	1.20		0.021
			415.70	417.00	D925932	1.30		0.022
			417.00	418.50	D925933	1.50		0.025
			418.50	420.00	D925934	1.50		<0.005
			420.00	421.50	D925935	1.50		0.005
			421.50	423.00	D925936	1.50		0.026
			423.00	424.50	D925937	1.50		0.006
424.30	424.31	Py10	424.50	426.00	D925938	1.50		0.022
		<b>Pyrite 10%</b>	426.00	427.50	D925940	1.50		0.204
		HP, 14-09-10: 2-3 mm wide wedge shaped massive Py veinlet associated with a 1 cm wide Qtz-Cb-Chl-Ser vein @ 45 DTCA	427.50	429.00	D925941	1.50		0.186
			429.00	430.00	P011219	1.00		<0.005
430.00	440.70	Py02	430.00	431.00	P011220	1.00		0.168
		<b>Pyrite 02%</b>	431.00	432.00	P011221	1.00		0.202
		Cm to dm zones of 1-2% very fine disseminated pyrite in light siliceous syenite.	432.00	433.00	P003674	1.00		0.083
			433.00	434.00	P003675	1.00		0.053
			434.00	435.00	P003676	1.00		0.055

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
440.90	453.00	Chl  <b>Chloritisation</b> Light pervasive chloritisation in addition to the light chloritisation in dark green stringers.	435.00	436.00	P003677	1.00	0.099		0.099
			436.00	437.00	P011222	1.00	0.397		0.397
			437.00	438.00	P011223	1.00	0.301		0.301
			438.00	439.00	P003680	1.00	0.041		0.041
			439.00	440.00	P011224	1.00	0.245		0.245
			440.00	441.00	P011225	1.00	0.621		0.621
			441.00	442.50	204996	1.50	0.211		0.211
			442.50	444.00	204997	1.50	0.403		0.403
			444.00	445.50	204998	1.50	0.056		0.056
			445.50	447.00	D925942	1.50	0.045		0.045
			447.00	448.50	D925943	1.50	0.231		0.231
			448.50	450.00	D925944	1.50	0.203		0.203
			450.00	451.50	D925945	1.50	0.282		0.282
			451.50	453.00	D925946	1.50	0.726		0.726
			453.00	454.50	D925947	1.50	0.223		0.223
455.40	456.00	STW;10%;Qz Cb Cl;T;40°;Py00.1; <b>Stockwerk 10% Quartz Carbonate Chlorite Tension 40° Pyrite 0.1%</b> HP, 14-09-10: Set of at least 18 Qtz, minor Cb, Chl, veinlets generally @ 40 DTCA, trace disseminated Py and Py along veinlet margins locally; up to 0.2% disseminated Py in slightly silicified wall rock locally	454.50	456.00	D925948	1.50	0.934		0.934
			456.00	457.50	D925950	1.50	0.116		0.116
			457.50	459.00	D925951	1.50	<0.005		0.001
			459.00	460.50	204999	1.50	0.015		0.015
459.80	460.10	BRE <b>Breccia 55°</b> Angular syenite fragments in a white Qz matrix.	460.50	462.00	205000	1.50	0.936		0.936
			462.00	463.00	P011226	1.00	0.381		0.381
			463.00	464.00	P011227	1.00	1.010		1.010
463.80	500.50	Sil; Alb; Chl <b>Silicification; Albitisation; Chloritisation</b> Light to moderate pervasive smokey silicification and loc brecciated with light and chloritisation.  HP, 14-09-10: Interval change from (463.8-482.5) to (463.8-500.5); besides silicification rock is moderately to highly fractured with Chl-coated fractures and Chl veinlets; local breccia zones have Cb matrix or Chl matrix							
			464.00	465.00	P011228	1.00	2.120		2.120



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
<b>Pyrite 03%</b>	465.00	466.00	P011229	1.00	2.860		2.860
2-4% very fine disseminated pyrite in a siliceous matrix.	466.00	467.10	P011230	1.10	1.145		1.145
	467.10	468.00	P011232	0.90	1.795		1.795
HP, 14-09-10: Interval change from (463.8-482.5) to (463.8-500.5); 0.5-5% Py, also as fracture fill and in stringers	468.00	469.00	P011233	1.00	0.808		0.808
	469.00	470.00	P011234	1.00	0.555		0.555
	470.00	471.00	P011235	1.00	0.535		0.535
	471.00	472.00	P011236	1.00	0.557		0.557
	472.00	473.00	P011237	1.00	0.409		0.409
	473.00	474.00	P011238	1.00	0.460		0.460
	474.00	475.00	P011239	1.00	0.952		0.952
	475.00	476.00	P011240	1.00	0.865		0.865
	476.00	477.00	P011241	1.00	0.442		0.442
	477.00	478.00	P011242	1.00	0.625		0.625
	478.00	479.00	P011243	1.00	1.150		1.150
	479.00	480.00	P011244	1.00	1.325		1.325
	480.00	481.00	P011245	1.00	1.070		1.070
	481.00	482.00	P011246	1.00	0.193		0.193
	482.00	483.00	P011247	1.00	0.571		0.571
	483.00	484.00	P003706	1.00	0.168		0.168
	484.00	485.00	P003707	1.00	0.158		0.158
	485.00	486.00	P003708	1.00	0.350		0.350
	486.00	487.00	P011271	1.00	0.237		0.237
	487.00	488.00	P011272	1.00	0.355		0.355
	488.00	489.00	P011273	1.00	2.100		2.100
	489.00	490.00	P011274	1.00	0.022		0.022
	490.00	491.00	P011275	1.00	2.850		2.850
	491.00	492.00	P011276	1.00	7.140	7.31	7.310
	492.00	493.00	P011277	1.00	3.120	3.36	3.360
	493.00	494.00	203751	1.00	1.070		1.070
	494.00	495.00	203752	1.00	1.910		1.910
	495.00	496.50	203753	1.50	0.350		0.350
	496.50	498.00	203754	1.50	0.466		0.466
	498.00	499.00	203755	1.00	1.475		1.475

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			499.00	500.00	203756	1.00	0.250		0.250
			500.00	501.00	P011278	1.00	2.780		2.780
500.50	500.90	Sil <b>Silicification</b> Light pervasive smokey silicification brecciated.							
500.50	500.90	Py02 <b>Pyrite 02%</b> 2% very fine disseminated pyrite in a siliceous syenite.	501.00	502.00	P003717	1.00	0.064		0.064
			502.00	503.00	P011279	1.00	1.210		1.210
502.70	505.90	Py02 <b>Pyrite 02%</b> 2% very fine disseminated pyrite in a siliceous syenite.	503.00	504.00	P011280	1.00	3.040	2.96	2.960
			504.00	505.00	P011281	1.00	5.920	5.80	5.800
			505.00	506.00	P011282	1.00	0.812		0.812
			506.00	507.00	P011283	1.00	0.736		0.736
			507.00	508.50	203757	1.50	0.171		0.171
			508.50	510.00	203758	1.50	0.079		0.079
			510.00	511.50	203759	1.50	0.120		0.120
			511.50	513.00	203760	1.50	0.010		0.010
513.00	514.50	Py01 <b>Pyrite 1%</b> HP, 14-09-10: Up to 1% Py as disseminations and in mm-sized aggregates over a few cm locally	513.00	514.50	203762	1.50	0.326		0.326
513.70	551.20	BA; MSF; FOL; O; BR <b>Mafic Meta-Volcanic ; Mudslate; Foliation ; Laminated; Brecciated</b> Grauwacke locally interbedded with graphitic argillite. Light foliation @ 50° TCA and non magnetic. Locally brecciated. Graywacke: pale green, fine grained matrix Light foliation. Graphitic argillite: black aphanitic matrix. Tr-1% Cc veins @ 50-60° TCA. Light carbonatization and chloritisation. 1-2% pyrite, mostly in the graphitic argillite. Upper contact @ 45° TCA.  HP, 14-09-10: Rock is Mafic Metavolcanics, not Greywacke, intercalated with about 10% black graphitic argillite; mafic metavolcanics are pale to medium green in colour and very fine-grained, moderately foliated with foliation @ 45 DTCA, chloritized, locally fine-grained due to pervasive Cc carbonatization over 0.5 - 1.0 m, locally brecciated over 0.2 - 0.5 m with foliation parallel elongated	514.50	516.00	D925952	1.50	0.016		0.016
			516.00	517.50	D925953	1.50	<0.005		0.001
			517.50	519.00	D925954	1.50	<0.005		0.001
			519.00	520.50	D925956	1.50	0.006		0.006
			520.50	522.00	D925957	1.50	<0.005		0.001
			522.00	523.50	D925958	1.50	<0.005		0.001
			523.50	525.00	D925960	1.50	<0.005		0.001
			525.00	526.50	D925961	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
525.60	525.65	<p>fragments in a Chl matrix; black argillite occurs in 0.5 - 6 cm wide intercalations that are generally foliation parallel, locally @ 80 DTCA, occasionally with mm wide massive Py laminations or with Py disseminations or up to 30% Py aggregates; some breccia zones consist of foliation parallel disrupted mm scale laminations of intercalated argillite and mafic metavolcanics</p> <p>(513.7-515.2) Well foliated pervasively Cc carbonatized mafic metavolcanics, foliation @ 45 DTCA, rock has the appearance of a breccia but consists of mm sized Cc grains - aggregates in a Chl-rich matrix, gradational lower contact</p> <p>Lower contact of interval is gradational over 5-10 cm (mm wide intercalations of mafic metavolcanics and underlying ultramafics), laminations @ 70 DTCA</p> <p>Sp02; Py10</p> <p><b>Sphalerite 2%; Pyrite 10%</b></p> <p>HP, 14-09-10: 2% mm-sized Sph aggregates and 10% 2 mm wide massive Py laminations in a 4 cm wide Cc vein @ 45 DTCA</p>	526.50	528.00	D925962	1.50	<0.005		0.001
			528.00	529.50	D925963	1.50	<0.005		0.001
			529.50	531.00	D925964	1.50	<0.005		0.001
			531.00	532.50	D925965	1.50	<0.005		0.001
			532.50	534.00	D925966	1.50	<0.005		0.001
			534.00	535.50	D925967	1.50	<0.005		0.001
			535.50	537.00	D925968	1.50	<0.005		0.001
			537.00	538.50	D925970	1.50	<0.005		0.001
			538.50	540.00	D925971	1.50	<0.005		0.001
			540.00	541.50	D925972	1.50	<0.005		0.001
			541.50	543.00	D925973	1.50	0.005		0.005
			543.00	544.50	D925974	1.50	<0.005		0.001
			544.50	546.00	D925975	1.50	<0.005		0.001
			546.00	547.50	D925976	1.50	<0.005		0.001
			547.50	549.00	D925977	1.50	0.008		0.008
549.00	550.00	<p>FRC</p> <p><b>Fractured</b></p> <p>Broken core.</p> <p>HP, 15-09-10: Slivers of graphitic argillite and brecciated mafic metavolcanics; some powdery - flakey fault gouge material; interval includes one 10 cm wide massive barren Qtz vein @ 45 DTCA</p>	549.00	550.00	D925978	1.00	<0.005		0.001
			550.00	551.00	P003723	1.00	0.020		0.020
550.80	551.00	Py75	551.00	552.00	P003724	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<p><b>Pyrite 75%</b> 70-80% pyrite with calcite.</p> <p>HP, 15-09-10: Fractured massive Py occurs in a 20 cm wide layer @ 70 DTCA; sharp contacts</p> <p>Car; Ser</p> <p><b>Carbonatisation; Sericitisation</b> Moderate carbonatisation in injections and light sericitisation.</p>							
551.10	579.00								
551.20	574.00	<p>UM; RUB; LAM; FOL</p> <p><b>Ultramafic Volcanic (incl. Flows) 70°; Banded; Parallel laminations; Foliation</b></p> <p>HP, 15-09-10: Ultramafic volcanics; pale to medium green, medium grey and black; talc-serpentine - rich; banded - laminated with alternating 0.5 - 2 cm, locally up to 20 cm, wide ultramafic volcanics and 35-65% Cc, minor Qtz, veinlets - veins; rare black argillite laminations as well; laminations and foliation @ 70-80 DTCA; rare cm wide laminations with up to 10% disseminated mm-sized Py aggregates; sharp lower contact @ 70 DTCA</p>	552.00	553.50	D925980	1.50	<0.005		0.001
			553.50	555.00	D925981	1.50	0.005		0.005
			555.00	556.50	D925982	1.50	<0.005		0.001
			556.50	558.00	D925983	1.50	<0.005		0.001
			558.00	559.50	D925984	1.50	0.032		0.032
			559.50	561.00	D925985	1.50	0.967		0.967
			561.00	562.50	D925986	1.50	0.005		0.005
			562.50	564.00	D925987	1.50	0.005		0.005
			564.00	565.50	D925988	1.50	0.181		0.181
			565.50	567.00	D925990	1.50	0.023		0.023
			567.00	568.50	D925991	1.50	0.006		0.006
			568.50	570.00	D925992	1.50	<0.005		0.001
			570.00	571.50	D925993	1.50	0.032		0.032
			571.50	573.00	D925994	1.50	0.114		0.114
			573.00	574.00	D925995	1.00	0.117		0.117
574.00	579.00	<p>MS; GW; FOL; LAM</p> <p><b>Mudslate 70°; Wacke (greywacke); Foliation ; Parallel laminations</b></p> <p>HP, 15-09-10: Black graphitic argillite intercalated with 20% 1-50 cm wide sericitized greywacke; foliation - laminations @ 70 DTCA; locally convoluted laminations; lower 1 m contains 50% up to 10 cm wide barren Qtz-Cc veinlets - veins</p>							
574.00	579.00	<p>GP</p> <p><b>Graphite</b></p> <p>Graphitic argillite. Foliated @ 70° TCA and non magnetic.</p> <p>Black aphanitic matrix with small folds interbedded with graywacke.</p> <p>Moderate carbonatisation in injections.</p> <p>1-2% laminated pyrite and in (HP, 1-2 cm sized) blebs.</p>	574.00	575.50	D925996	1.50	0.177		0.177
			575.50	576.80	D925998	1.30	0.226		0.226
			576.80	578.00	D926000	1.20	0.149		0.149
			578.00	579.00	D926001	1.00	0.046		0.046

579.00

Fin du sondage

Nombre d'échantillons : 458

Nombre d'échantillons QAQC : 43

Longueur totale échantillonnée : 575.30

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.00	13.50	D925769	D925768	1.50	<0.005	0.001
25.50	25.50	D925779	O54Pa	0.00	2.980	2.980
38.00	39.50	D925789	D925788	1.50	0.017	0.017
45.50	45.50	D925795	m	0.00	<0.005	0.001
49.70	49.70	D925799	O52Pb	0.00	0.366	0.366
66.00	67.50	D925809	D925808	1.50	<0.005	0.001
72.00	72.00	P003539	O52Pb	0.00	0.328	0.328
81.00	81.00	D925819	O53Pb	0.00	0.653	0.653
102.00	102.00	P003556	O52Pb	0.00	0.329	0.329
114.00	115.50	204961	O50Pb	1.50	0.865	0.865
145.50	147.00	D925829	D925828	1.50	0.048	0.048
153.00	153.00	D925835	m	0.00	<0.005	0.001
157.50	157.50	D925839	O54Pa	0.00	2.890	2.890
175.50	177.00	D925849	D925848	1.50	<0.005	0.001
189.00	189.00	D925859	O52Pb	0.00	0.314	0.314
202.00	202.00	P003582	O53Pb	0.00	0.640	0.640
211.50	213.00	D925869	D925868	1.50	0.019	0.019
219.00	219.00	D925875	m	0.00	<0.005	0.001
223.50	223.50	D925879	O53Pb	0.00	0.629	0.629
244.90	244.90	P003600	O54Pa	0.00	2.900	2.900
256.50	258.00	D925889	D925888	1.50	<0.005	0.001
277.40	277.40	D925899	O54Pa	0.00	0.736	0.736
281.00	281.00	228848	O52Pb	0.00	0.316	0.316
294.00	295.50	D925909	D925908	1.50	<0.005	0.001
301.50	301.50	D925915	m	0.00	<0.005	0.001
306.00	306.00	D925919	O52Pb	0.00	0.311	0.311
321.50	323.00	204981	O54Pa	1.50	3.010	2.960
349.50	351.00	D925929	D925928	1.50	0.006	0.006
355.00	355.00	P003626	O52Pb	0.00	0.324	0.324
376.00	376.00	P003648	O54Pa	0.00	2.940	2.940
399.00	399.00	P011213	O53Pb	0.00	0.626	0.626
424.50	424.50	D925939	O53Pb	0.00	0.618	0.618
454.50	456.00	D925949	D925948	1.50	0.584	0.584

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
466.00	466.00	P011231	O52Pb	0.00	0.320	0.320
482.00	482.00	P003705	O54Pa	0.00	2.880	2.880
511.50	513.00	203761	O50Pb	1.50	0.852	0.852
517.50	517.50	D925955	m	0.00	<0.005	0.001
522.00	522.00	D925959	O54Pa	0.00	2.950	2.950
535.50	537.00	D925969	D925968	1.50	<0.005	0.001
549.00	549.00	D925979	O52Pb	0.00	0.323	0.323
564.00	565.50	D925989	D925988	1.50	0.167	0.167
574.00	574.00	D925997	m	0.00	<0.005	0.001
575.50	575.50	D925999	O53Pb	0.00	0.620	0.620

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-54	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multi Drill	Lot :	
Décrit par : Dominic Fleming	Du : 2009-05-11	Date de description : 2009-05-15
	Au : 2009-05-12	

Collet

Azimut : 326.51°  
 Plongée : -64.00°  
 Longueur : 107.00 m

UTM

Est	630 048.6
Nord	5 374 369.5
Élévation	283.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	324.25°	-63.70°	Non
Reflex	60.00	325.65°	-62.40°	Non
Reflex	90.00	325.85°	-60.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

GPS Datum NAD 83 Zone 17

Hole surveyed (Nov 2009) by Descarreaux.

Resampled by Hillar Pintson, May 2010

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	8.50	MT; LOST <b>Casing; Core Not Recovered</b> Casing (HP: interval change to 8.5 m)							
8.50	97.20	SY POR; POR; PT <b>Syenite Porphyry Intrusive; Porphyric; Lath</b> Dark red-green to purple. No quartz vein. Few fractures filled with silica-carbonate fluids, boudinage. Stringers of epidote. Fld euhedral phenos (40%) (2-5mm) and Fld lath (10%) (3mmX5mm).  Fld laths locally completely altered and in the foliation. Foliation 30-40 TCA. Fld phenos 25% (3-4mm).  Alterations : Strong epidote, weak potassic, medium ALB, medium SR and medium CL.  Breccia from 89.65m to 89.77m, matrix silicate and 10% calco. (HP: not Chalcopyrite, but Py)  Fine disseminated Py, 1% associate with epidote. Disseminated magnetite (15-20%), mag +++++.  (HP): (16.0-18.0) some Limonite-coated fractures, some broken core	8.50	10.00	D922453	1.50	0.007		0.007
			10.00	11.50	D922454	1.50	<0.005		0.001
			11.50	13.00	D922455	1.50	<0.005		0.001
			13.00	14.00	P008389	1.00	0.031		0.031
			14.00	15.00	P008390	1.00	0.094		0.094
			15.00	16.00	P008391	1.00	0.432		0.432
			16.00	17.00	D922456	1.00	0.304		0.304
			17.00	18.00	D922457	1.00	0.028		0.028
			18.00	19.00	P008392	1.00	<0.005		0.001
			19.00	20.00	P008393	1.00	<0.005		0.001
			20.00	21.00	P008394	1.00	0.006		0.006
			21.00	22.00	P008395	1.00	0.008		0.008
			22.00	23.00	P008396	1.00	<0.005		0.001
			23.00	24.00	D922458	1.00	0.005		0.005
			24.00	25.50	D922460	1.50	<0.005		0.001
			25.50	27.00	D922461	1.50	<0.005		0.001
			27.00	28.50	D922462	1.50	<0.005		0.001
			28.50	30.00	D922463	1.50	0.017		0.017
			30.00	31.50	D922464	1.50	<0.005		0.001
31.30	31.45	FRC <b>Fractured 20°</b> fracture	31.50	33.00	D922465	1.50	<0.005		0.001
			33.00	34.50	D922466	1.50	<0.005		0.001
			34.50	36.00	D922467	1.50	<0.005		0.001
			36.00	37.50	D922468	1.50	0.009		0.009
			37.50	39.00	D922470	1.50	0.013		0.013
39.00	40.50	FOL; CIS <b>Foliation 20°; Sheared</b> Fractured and (minor) broken core  (HP): interval change; moderately developed shear zone, foliation @ 20 DTCA; gradational upper and lower contacts	39.00	40.50	D922471	1.50	0.113		0.113
			40.50	42.00	D922472	1.50	0.006		0.006
			42.00	43.50	D922473	1.50	<0.005		0.001
			43.50	45.00	D922474	1.50	0.014		0.014
			45.00	46.50	D922476	1.50	0.009		0.009
			46.50	48.00	D922477	1.50	0.014		0.014
			48.00	49.50	D922478	1.50	0.285		0.285

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			49.50	51.00	D922480	1.50		0.522		0.522
			51.00	52.50	D922481	1.50		1.710		1.710
			52.50	54.00	D922482	1.50		0.130		0.130
			54.00	55.50	D922483	1.50		0.007		0.007
			55.50	57.00	D922484	1.50		<0.005		0.001
			57.00	58.50	D922485	1.50		0.007		0.007
			58.50	60.00	D922486	1.50		<0.005		0.001
			60.00	61.50	D922487	1.50		0.006		0.006
			61.50	63.00	D922488	1.50		0.008		0.008
			63.00	64.00	D922490	1.00		0.005		0.005
			64.00	64.90	D922491	0.90		<0.005		0.001
			64.90	66.00	P008397	1.10		0.035		0.035
			66.00	67.00	P008398	1.00		0.059		0.059
			67.00	68.00	P008399	1.00		0.615		0.615
67.65	67.85	VEI;6;Cc;T;40°;; <b>Vein 6 Calcite Tension 40°</b> 6 cm wide massive white and pink Cc vein; contains several mm-cm sized slivers of angular wall rock xenoliths; barren	68.00	69.00	D922492	1.00		0.011		0.011
			69.00	70.50	D922493	1.50		0.007		0.007
			70.50	72.00	D922494	1.50		0.067		0.067
			72.00	73.00	P008400	1.00		0.069		0.069
			73.00	74.00	D922495	1.00		0.125		0.125
73.30	73.80	FRC <b>Fractured</b> fracture and broken core								
73.80	93.00	FOL <b>Foliation 40°</b> fol40	74.00	75.00	D922496	1.00		0.342		0.342
			75.00	76.50	D922497	1.50		0.106		0.106
			76.50	78.00	D922498	1.50		0.079		0.079
			78.00	79.50	D922500	1.50		0.006		0.006
			79.50	81.00	D922501	1.50		0.009		0.009
			81.00	82.50	D922502	1.50		0.073		0.073
			82.50	84.00	D922503	1.50		0.015		0.015
			84.00	85.50	D922504	1.50		<0.005		0.001
			85.50	87.00	D922505	1.50		0.007		0.007
			87.00	88.00	D922506	1.00		0.010		0.010
			88.00	89.00	D922507	1.00		0.183		0.183
			89.00	90.00	P008401	1.00		0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
97.20	107.00	SY; BSF <b>Syenite; Breccia Silicified zone</b> Brecciated syenite. Gray. Strong silicification, medium epidotisation, medium carbonatation, medium albitisation and medium chlorite. Strong pervasive SR.  Few phenos altered.  Intense fractures (60%). Matrix silica and carbonate. Micro-fractures filled with chlorite. 3% disseminated Py. Upper contact 40 TCA.  Drill hole hit a drift at 107m.  E.O.H. : 107m	90.00	91.00	D922508	1.00	0.592		0.592
			91.00	92.00	P008402	1.00	0.193		0.193
			92.00	93.00	P008403	1.00	0.202		0.202
			93.00	94.50	D922510	1.50	0.428		0.428
			94.50	96.00	D922511	1.50	0.051		0.051
			96.00	97.00	P008415	1.00	0.110		0.110
			97.00	98.00	P008404	1.00	2.570		2.570
			97.20	107.00	Py03	98.00	99.00	P008405	1.00
97.20	107.00	<b>Pyrite 03%</b> Few phenos altered.  Intense fractures (60%). Matrix silica and carbonate. Micro-fractures filled with chlorite. 3% disseminated Py.	99.00	100.00	P008406	1.00	1.170		1.170
			100.00	101.00	P008408	1.00	1.325		1.325
			101.00	102.00	P008409	1.00	0.796		0.796
			102.00	103.00	P008410	1.00	0.673		0.673
			103.00	104.00	P008411	1.00	0.463		0.463
			104.00	105.00	P008412	1.00	0.274		0.274
			105.00	106.00	P008413	1.00	1.185		1.185
			106.00	107.00	P008414	1.00	4.180		4.180
107.00	Fin du sondage Nombre d'échantillons : 78 Nombre d'échantillons QAQC : 8 Longueur totale échantillonnée : 98.50								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
23.00	23.00	D922459	O52Pb	0.00	0.303	0.303
36.00	37.50	D922469	D922468	1.50	0.009	0.009
43.50	43.50	D922475	m	0.00	<0.005	0.001
48.00	48.00	D922479	O53Pb	0.00	0.618	0.618
61.50	63.00	D922489	D922488	1.50	0.006	0.006
76.50	76.50	D922499	O54Pa	0.00	2.860	2.860
90.00	91.00	D922509	D922508	1.00	0.477	0.477
99.00	99.00	P008407	O53Pb	0.00	0.666	0.666

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-55	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multi Drill	Lot :	
Décrit par : Dominic Fleming	Du : 2009-05-12	Date de description : 2009-05-21
	Au : 2009-05-15	

Collet

Azimut : 359.08°  
 Plongée : -64.30°  
 Longueur : 106.40 m

UTM

Est	630 006.8
Nord	5 374 350.2
Élévation	283.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	1.55°	-63.30°	Non
Reflex	60.00	2.25°	-62.70°	Non
Reflex	90.00	5.75°	-62.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

GPS Datum NAD83, UTM Zone 17.

Resampled 11/09/10 by K.Wallace

\*\*indicates changes made

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	7.30	MT <b>Casing</b> Casing 7.3m							
7.30	93.70	SY PT POR; PT; POR <b>Syenite Lath Porphyry Intrusive; Lath; Porphyric</b> Dark-red purple. 25% Fld laths (2-3mm X 3-5mm) and 15% Fld euhedrals (2-5mm). Fine to medium grains. Weak ALB alteration of the Fld. Micro-fractures and anastomose veinlets(5%-10%) filled with silica-carbonate fluids. Pervasive bleach and weathering (rust).  Alteration: Weak CARB, weak SI, medium ALB, medium CL, medium potassic and medium Epidote. Foliation well developed 30-40 TCA.  Vuggy intervals between 61m and 68m.  10-15 % disseminated magnetite. Mag +++. Trace to no mineralization.	7.30	9.00	D911042	1.70	0.005		0.005
8.00	51.20	FOL; FRC <b>Foliation 40°; Fractured</b> fol and fract  Sheared from 29.00-33.00m	9.00	10.50	D911043	1.50	0.018		0.018
			10.50	12.00	D911044	1.50	0.194		0.194
			12.00	13.50	D911046	1.50	0.006		0.006
			13.50	15.00	D911047	1.50	0.017		0.017
			15.00	16.50	D911048	1.50	0.007		0.007
			16.50	18.00	D911049	1.50	0.009		0.009
			18.00	19.00	D911051	1.00	0.043		0.043
			19.00	20.00	D911052	1.00	0.015		0.015
20.20	23.40	Sil40; Epi25 <b>Silicification 40; Epidotisation 25</b> strong alt.	20.00	21.00	P008836	1.00	0.005		0.005
			21.00	22.00	P008837	1.00	0.013		0.013
			22.00	23.00	P008838	1.00	0.005		0.005
			23.00	24.00	P008839	1.00	<0.005		0.001
			24.00	25.50	D911053	1.50	<0.005		0.001
			25.50	27.00	D911054	1.50	0.055		0.055
			27.00	27.90	D911055	0.90	<0.005		0.001
			27.90	28.90	P008840	1.00	0.006		0.006
28.90	33.00	Sil20; Wea50 <b>Silicification 20; Weathering (Incl. Saprolitic alter.) 50</b> weathering	28.90	29.90	P008841	1.00	0.006		0.006
			29.90	30.90	P008843	1.00	0.005		0.005
			30.90	31.90	P008844	1.00	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			31.90	32.90	P008845	1.00		0.034		0.034
			32.90	33.90	P008846	1.00		0.013		0.013
			33.90	35.00	D911056	1.10		<0.005		0.001
			35.00	36.00	D911057	1.00		<0.005		0.001
			36.00	37.50	D911058	1.50		0.008		0.008
			37.50	39.00	D911059	1.50		<0.005		0.001
			39.00	40.50	D911061	1.50		<0.005		0.001
			40.50	42.00	D911062	1.50		<0.005		0.001
			42.00	43.50	D911063	1.50		<0.005		0.001
			43.50	45.00	D911064	1.50		<0.005		0.001
			45.00	46.50	D911065	1.50		0.005		0.005
			46.50	48.00	D911066	1.50		0.036		0.036
			48.00	49.70	D911067	1.70		0.267		0.267
			49.70	51.30	D911068	1.60		0.112		0.112
51.20	51.44	FRC <b>Fractured 10°</b> fracture	51.30	52.30	P008847	1.00		0.053		0.053
51.90	52.35	FRC <b>Fractured 60°</b> Fracture and broken core	52.30	53.30	P008848	1.00		0.132		0.132
52.90	58.20	Sil30; Alb25; Chl20 <b>Silicification 30; Albitisation 25; Chloritisation 20</b> strong alt.	53.30	54.30	P008849	1.00		0.186		0.186
			54.30	55.30	P008850	1.00		0.070		0.070
			55.30	56.30	P008851	1.00		0.016		0.016
55.70	56.80	Sil30; Alb25; Chl20 FRC <b>Fractured 60°</b> fracture and broken core	56.30	57.30	P008852	1.00		0.034		0.034
56.80	75.00	FOL <b>Foliation 45°</b> strong fol. 45	57.30	58.30	P008853	1.00		0.052		0.052
57.60	58.30	B <b>Breccia</b> Breccia. Dark-green to orange-red-green. 70% Phenos (3-20mm) wheatered. Matrix chlorite and calcite. Sharp upper contact 30 TCA and lower contact 35 TCA. No mineralization.	58.30	59.30	P008854	1.00		0.028		0.028
			59.30	60.00	D911069	0.70		0.008		0.008
			60.00	61.50	D911071	1.50		0.005		0.005
			61.50	63.00	D911072	1.50		<0.005		0.001
			63.00	64.50	D911073	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			64.50	66.00	D911074	1.50		0.006	0.006
			66.00	67.50	D911075	1.50		<0.005	0.001
			67.50	69.00	D911076	1.50		0.009	0.009
			69.00	70.00	D911077	1.00		0.005	0.005
			70.00	71.00	P008855	1.00		0.005	0.005
			71.00	72.00	P008856	1.00		0.043	0.043
			72.00	73.00	P008857	1.00		0.013	0.013
			73.00	74.00	P008858	1.00		0.014	0.014
			74.00	75.00	P008860	1.00		0.026	0.026
			75.00	76.00	P008861	1.00		0.006	0.006
			76.00	77.00	D911078	1.00		0.009	0.009
			77.00	78.00	D911079	1.00		0.024	0.024
			78.00	79.50	D911081	1.50		<0.005	0.001
			79.50	81.00	D911082	1.50		<0.005	0.001
			81.00	82.50	D911083	1.50		0.006	0.006
			82.50	84.00	D911084	1.50		<0.005	0.001
			84.00	85.50	D911086	1.50		<0.005	0.001
			85.50	87.00	D911087	1.50		<0.005	0.001
			87.00	88.50	D911088	1.50		<0.005	0.001
			88.50	90.00	D911089	1.50		0.005	0.005
			90.00	90.50	D911091	0.50		<0.005	0.001
			90.50	91.50	P008862	1.00		0.007	0.007
			91.50	92.50	P008863	1.00		0.008	0.008
			92.50	93.50	P008864	1.00		0.007	0.007
93.30	93.70	VEI;40;CcFpPg;;30°; <b>Vein 40 Calcite Feldspath (alkaline) Plagioclase 30°</b> vein silica-carbonate	93.50	94.00	P008865	0.50		0.005	0.005
93.70	106.40	BSF <b>Breccia silicified zone</b> Breccia. Gray. Strong silicification, weak epidotisation, medium carbonatation, medium albitisation and medium chlorite. Strong pervasive SR. Aphanitic to fine grains.  Intense fractures (45%). Matrix silica and carbonate. Micro-fractures filled with silica-carbonate fluids. 3% disseminated Py. Upper contact							



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
93.70	106.40	Py05 <b>Pyrite 5%</b> 5 to 10% disseminated Py						
93.90	106.40	Sil <b>Silicification</b> Strong alt.	94.00	95.00	P008866	1.00	0.057	0.057
			95.00	96.00	P008867	1.00	1.620	1.620
			96.00	97.00	P008868	1.00	2.570	2.570
		Sil60; Alb10; Epi10; Ser30; Chl10	97.00	98.00	P008869	1.00	0.242	0.242
			98.00	99.00	P008870	1.00	2.870	2.870
		Silicification 60; Albitisation 10; Epidotisation 10; Sericitisation 30; Chloritisation 10	99.00	100.00	P008871	1.00	3.630	3.630
			100.00	101.00	P008872	1.00	2.560	2.560
			101.00	102.00	P008873	1.00	4.080	5.010
			102.00	103.00	P008874	1.00	2.760	2.760
			103.00	104.00	P008876	1.00	2.280	2.280
			104.00	105.00	P008877	1.00	2.400	2.400
			105.00	105.70	P008878	0.70	5.100	5.100
			105.70	106.40	P008879	0.70	3.350	3.350
106.40	<b>Fin du sondage</b> Nombre d'échantillons : 84 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 99.10							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.50	10.50	D911045	m	0.00	<0.005	0.001
16.50	16.50	D911050	O52Pb	0.00	0.318	0.318
28.90	28.90	P008842	O52Pb	0.00	0.319	0.319
37.50	39.00	D911060	D911059	1.50	0.005	0.005
59.30	59.30	D911070	O53Pb	0.00	0.634	0.634
73.00	73.00	P008859	O53Pb	0.00	0.635	0.635
77.00	78.00	D911080	D911079	1.00	0.029	0.029
82.50	82.50	D911085	m	0.00	<0.005	0.001
88.50	88.50	D911090	O54Pa	0.00	3.010	3.010
102.00	102.00	P008875	O54Pa	0.00	2.880	2.880

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-56	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multi Drill	Lot :	
Décrit par : Dominic Fleming	Du : 2009-05-15	Date de description : 2009-05-22
	Au : 2009-05-16	

Collet

Azimut : 170.00°  
 Plongée : -90.00°  
 Longueur : 60.00 m

UTM

Est	629 974.6
Nord	5 374 324.2
Élévation	282.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	314.15°	-88.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

UTM NAD 83 Z17

\*\* Bit broke in the hole at 60m. E.O.H. : 60m \*\*

Resampled July 27, 2010 - K. Wallace.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	12.10	MT <b>Casing</b> Casing 12.1m							
12.10	60.00	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Purple to purple-pink-red. 5-10% euhedrals Fld phenos (2-4mm) and 20-30% euhedrals phenos after 39.3m. Phenos weakly potassic and CL altered. 1-2% lath Fld. Fine to medium grains.  Foliation 40-50 TCA. Few micro-fractures (1%) filled with silica-carbonate fluids (albitized). Increase of the micro-fractures after 30m to 5%.  Alterations: weak to medium potassic, medium CL.  Fine magnetite disseminated. Mag ++++  Traces of Py to no mineralization  Bit broke in the hole at 60m  E.O.H. : 60m	12.80	14.00	D909606	1.20	0.400		0.400
			14.00	15.00	P009354	1.00	0.297		0.297
			15.00	16.00	P009355	1.00	0.008		0.008
			16.00	17.00	P009356	1.00	0.013		0.013
			17.00	18.00	P009357	1.00	<0.005		0.001
			18.00	19.50	D909607	1.50	<0.005		0.001
			19.50	21.00	D909608	1.50	0.006		0.006
			21.00	22.50	D909609	1.50	<0.005		0.001
			22.50	24.00	D909611	1.50	<0.005		0.001
			24.00	25.50	D909612	1.50	<0.005		0.001
			25.50	27.00	D909613	1.50	0.035		0.035
			27.00	28.00	P009358	1.00	<0.005		0.001
			28.00	29.00	P009360	1.00	0.007		0.007
			29.00	30.00	P009361	1.00	0.035		0.035
			30.00	31.00	P009362	1.00	0.391		0.391
			31.00	32.00	D909614	1.00	0.038		0.038
			32.00	33.00	D909615	1.00	<0.005		0.001
			33.00	34.50	D909616	1.50	0.006		0.006
			34.50	36.00	D909617	1.50	0.169		0.169
			36.00	37.50	D909618	1.50	0.038		0.038
			37.50	39.00	D909619	1.50	0.008		0.008
			39.00	40.50	D909621	1.50	<0.005		0.001
			40.50	42.00	D909622	1.50	0.005		0.005
			42.00	43.00	D909623	1.00	<0.005		0.001
			43.00	44.00	D909624	1.00	<0.005		0.001
			44.00	45.00	P009363	1.00	<0.005		0.001
			45.00	46.00	P009364	1.00	<0.005		0.001
			46.00	46.90	P009365	0.90	0.007		0.007
46.30	46.33	FAI <b>Fault</b> fault	46.90	48.00	D909625	1.10	<0.005		0.001
			48.00	49.50	D909626	1.50	0.008		0.008
			49.50	51.00	D909627	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	51.00	52.50	D909628	1.50	<0.005		0.001
	52.50	54.00	D909629	1.50	<0.005		0.001
	54.00	55.50	D909631	1.50	<0.005		0.001
	55.50	57.00	D909632	1.50	<0.005		0.001
	57.00	58.50	D909633	1.50	0.007		0.007
	58.50	60.00	D909634	1.50	0.037		0.037
60.00	Fin du sondage Nombre d'échantillons : 37 Nombre d'échantillons QAQC : 3 Longueur totale échantillonnée : 47.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
21.00	21.00	D909610	O52Pb	0.00	0.294	0.294
37.50	39.00	D909620	D909619	1.50	0.005	0.005
52.50	52.50	D909630	O53Pb	0.00	0.568	0.568



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	15.20	MT <b>Casing</b> Casing.	15.00	16.00	P009027	1.00	0.005		0.005
15.20	86.20	SY POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Grey-purple fine grained matrix with 2-4% Fp phenos (0.3-1cm). Massive and magnetic.  Light chloritisation pervasive + in stringers and carbonatisation in injections and veins @ 60° TCA.  Tr very fine disseminated pyrite, traces off chalcopyrite.  **abundant calcite veinlets and stringers - varied orientations. Increase in chlorite alteration below 61m - core is dark and has a greenish tinge.	16.00	17.00	P009028	1.00	0.009		0.009
			17.00	18.00	P009029	1.00	0.005		0.005
			18.00	19.00	P009030	1.00	<0.005		0.001
			19.00	20.00	P009031	1.00	<0.005		0.001
			20.00	21.00	P009032	1.00	0.012		0.012
			21.00	22.00	P009033	1.00	0.010		0.010
			22.00	23.00	P009034	1.00	0.005		0.005
			23.00	24.00	P009035	1.00	<0.005		0.001
			24.00	25.10	P009036	1.10	0.006		0.006
			25.10	26.20	P009037	1.10	0.038		0.038
			26.20	27.00	P009038	0.80	0.423		0.423
			27.00	28.00	P009040	1.00	<0.005		0.001
			28.00	29.00	P009041	1.00	0.009		0.009
			29.00	30.00	P009042	1.00	0.097		0.097
			30.00	31.00	P009043	1.00	0.477		0.477
			31.00	32.00	P009044	1.00	0.484		0.484
			32.00	33.00	P009045	1.00	0.021		0.021
			33.00	34.00	P009046	1.00	0.009		0.009
33.20	35.50	Py02 <b>Pyrite 02%</b> 1-2% very fine pyrite. Disseminated and in small veinlets.	34.00	35.00	P009047	1.00	0.557		0.557
			35.00	36.00	P009048	1.00	0.026		0.026
35.90	36.30	FRC <b>Fractured</b> Broken core with weathering.	36.00	37.00	P009049	1.00	0.027		0.027
			37.00	38.00	P009050	1.00	0.013		0.013
			38.00	39.00	P009051	1.00	0.005		0.005
			39.00	40.00	P009052	1.00	0.008		0.008
39.10	43.00	Hem <b>Hematisation</b> Reddish syenite. Light pervasive hematisation.	40.00	41.00	P009053	1.00	0.006		0.006
			41.00	42.00	P009054	1.00	<0.005		0.001
			42.00	43.00	P009055	1.00	0.009		0.009
			43.00	44.00	P009056	1.00	<0.005		0.001
			44.00	45.00	P009057	1.00	<0.005		0.001
			45.00	46.00	P009058	1.00	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
52.75	61.40	I2D POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> 5-7% Fp phenos (0.3-1cm).	46.00	47.00	P009059	1.00	<0.005		0.001
			47.00	48.00	P009060	1.00	0.017		0.017
			48.00	49.00	P009062	1.00	0.034		0.034
			49.00	50.00	P009063	1.00	0.007		0.007
			50.00	51.00	P009064	1.00	<0.005		0.001
			51.00	52.00	P009065	1.00	0.009		0.009
			52.00	53.00	P009066	1.00	0.011		0.011
			53.00	54.00	P009067	1.00	0.005		0.005
			54.00	55.00	P009068	1.00	0.014		0.014
			55.00	56.00	P009069	1.00	0.009		0.009
			56.00	57.00	P009070	1.00	0.005		0.005
			57.00	58.00	P009071	1.00	<0.005		0.001
			58.00	59.00	P009072	1.00	0.034		0.034
			59.00	60.00	P009073	1.00	0.008		0.008
60.00	61.00	P009074	1.00	0.008		0.008			
61.00	62.00	P009075	1.00	0.014		0.014			
61.40	72.30	Chl <b>Chloritisation</b> Light to moderate pervasive chloritisation.							
62.00	63.00	Py0.5 <b>Pyrite 0.5%</b> Tr-0.5% very fine disseminated pyrite (loc cubic).	62.00	63.00	P009076	1.00	0.028		0.028
			63.00	64.00	P009077	1.00	0.047		0.047
			64.00	65.00	P009078	1.00	0.007		0.007
			65.00	66.00	P009079	1.00	0.010		0.010
			66.00	67.00	P009080	1.00	0.014		0.014
			67.00	68.00	P009081	1.00	0.010		0.010
			68.00	69.00	P009083	1.00	0.005		0.005
			69.00	70.00	P009084	1.00	<0.005		0.001
			70.00	71.00	P009085	1.00	0.006		0.006
			71.00	72.00	P009086	1.00	0.010		0.010
72.00	73.00	P009087	1.00	1.055		1.055			
72.30	74.00	Silt; Car <b>Silicification; Carbonatisation</b> Light pervasive silicification and carbonatisation.	73.00	74.00	P009088	1.00	0.072		0.072
72.30	73.80	Py02							

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
73.80	74.00	<b>Pyrite 02%</b> 1-3% very fine disseminated pyrite.								
		Py04	74.00	75.00	P009089	1.00	0.098		0.098	
81.90	86.20	<b>Pyrite 04%</b> 3-5% very fine to fine disseminated pyrite in a calcitic syenite.	75.00	76.00	P009090	1.00	0.007		0.007	
		76.00	77.00	P009091	1.00	<0.005		0.001		
		77.00	78.00	P009092	1.00	0.020		0.020		
		78.00	79.00	P009093	1.00	0.024		0.024		
		79.00	80.00	P009094	1.00	0.028		0.028		
		80.00	81.00	P009095	1.00	<0.005		0.001		
		81.00	82.00	P009096	1.00	0.005		0.005		
		82.00	83.00	P009097	1.00	<0.005		0.001		
86.20	120.10	<b>Pyrite 03%</b> 2-4% fine to very fine pyrite. Disseminated and small veinlets.	83.00	84.00	P009098	1.00	0.026		0.026	
		84.00	85.00	P009099	1.00	0.127		0.127		
		85.00	86.00	P009100	1.00	0.065		0.065		
		86.00	87.00	P009101	1.00	0.036		0.036		
		87.00	88.00	P009103	1.00	0.244		0.244		
		88.00	89.00	P009104	1.00	0.986		0.986		
		<b>AN</b> Intermediate Volcanic (Flow) Interbedding of volcanic rock/chert/graphitic argillite. Green-greyish fine grained to aphanitic matrix. Moderate foliation @ 50° TCA.  Silicification and light carbonatisation and albitisation and loc light sericitisation.  2-3% pyrite. Disseminated and in small veinlets and blebs.  Upper contact sharp @ 45° TCA.  **Unit is as follows: 86.20-87.60 - mafic volcanics 87.60-102.10 - well defined sediments 102.10-120.10 - mafic volcanics with some sediments. - abundant qtz-carb veinlets/stringers typically aligned with foliation.								
		88.40	89.50	S10	89.00	90.00	P009105	1.00	0.110	
<b>Chert</b> Grey-black aphanitic matrix. Interbedding of chert and graphitic argillite.  Light foliation @ 55° TCA. Non magnetic.		90.00	91.00	P009106	1.00	0.009		0.009		
		91.00	92.00	P009107	1.00	0.017		0.017		
		92.00	93.00	P009108	1.00	0.042		0.042		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
92.30	102.10	Light carbonatisation.							
		3-4% pyrite. Disseminated and small veinlets.							
		Upper contact @ 55° TCA.							
		S10	93.00	94.00	P009109	1.00	0.013		0.013
		<b>Chert</b>	94.00	95.00	P009110	1.00	0.040		0.040
		Grey very hard aphanitic matrix. Massive (loc laminated @ 60° TCA) and non magnetic. Loc brecciated.	95.00	96.00	P009111	1.00	0.340		0.340
			96.00	97.00	P009112	1.00	0.228		0.228
		Light carbonatisation and albitisation? and light chloritisation in stringers.	97.00	98.00	P009113	1.00	0.395		0.395
			98.00	99.00	P009114	1.00	1.055		1.055
			99.00	100.00	P009115	1.00	0.266		0.266
		3-5% pyrite. Disseminated and small veinlets.	100.00	101.00	P009116	1.00	0.036		0.036
			101.00	102.00	P009117	1.00	0.008		0.008
			102.00	103.00	P009118	1.00	0.006		0.006
			103.00	104.00	D911092	1.00	0.005		0.005
			104.00	105.00	D911093	1.00	<0.005		0.001
			105.00	106.50	D911094	1.50	<0.005		0.001
			106.50	108.00	D911095	1.50	0.005		0.005
			108.00	109.50	D911096	1.50	<0.005		0.001
	109.50	111.00	D911097	1.50	0.005		0.005		
	111.00	112.00	D911098	1.00	<0.005		0.001		
	112.00	113.00	D911099	1.00	<0.005		0.001		
	113.00	114.00	P009120	1.00	2.570		2.570		
113.65	116.35	I2D POR	114.00	115.00	P009121	1.00	6.420	5.74	5.740
		<b>Syenite Porphyry Intrusive</b>	115.00	116.00	P009122	1.00	3.330	3.25	3.250
		Pale green to olive green aphanitic matrix with 2-4% Fp phenos (0.3-1cm).	116.00	117.00	P009123	1.00	0.012		0.012
		Massive and non magnetic.	117.00	118.50	D911101	1.50	0.757		0.757
			118.50	120.00	D911102	1.50	0.006		0.006
		1% Cc veins @ 15° TCA.	120.00	121.00	P009124	1.00	0.763		0.763
		Light epidotisation.							
		2-4% disseminated pyrite (loc cubic).							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
120.10	225.00	S <b>Sediment (Meta incl.)</b> Interbedding of graywacke and graphitic argillite. Pale green (aphanitic to fine grained) to black(aphanitic) matrix. Moderate foliation @ 50-60° TCA and non magnetic. Loc brecciated with flat angular graywacke fragments in a black graphitic matrix.  Light carbonatisation in injections and loc light chloritisation.  1% very fine to fine (loc cubic) disseminated pyrite (loc laminated in the graphitic argillite).  Arbitrary contact . The unit may start earlier, but the rock before looks more volcanics than sedimentary.  190.7-194.8: medium grained matrix. 204.2-213.6: medium grained matrix.  *- abundant qtz-carb veinlets/stringers typically aligned with foliation. Unit appears to have some mafic component as well, possibly could have placed last 2 units, as one from 86.20-225.00m.	121.00	122.00	P009125	1.00	0.634		0.634
120.10	124.00	GP <b>Graphite</b> Graphitic argillite. Black aphanitic laminated matrix with thin brecciated chert laminations (@ 50° TCA).  Light to moderate carbonatisation in injections.  3-5% disseminated pyrite and laminated pyrite.							
120.10	124.00	Upper contact sharp @ 50° TCA. Py04 <b>Pyrite 04%</b> 3-5% disseminated and laminated pyrite.							
122.40	125.00	FAI <b>Fault</b> Graphitic gouge, fractured core, Qz-calcite veins.	123.00	124.00	P009126	1.00	2.080		2.080
			124.00	125.00	D911103	1.00	0.045		0.045
			125.00	126.00	D911104	1.00	0.016		0.016
			126.00	127.30	D911105	1.30	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
127.50	127.80	VEI;30;QzCc;;35°;Py0.5; <b>Vein 30 Quartz Calcite 35° Pyrite0.5%</b> 30 cm Qz-Cc vein with traces of pyrite.	127.30	129.00	D911106	1.70	0.233		0.233
			129.00	130.50	D911107	1.50	0.007		0.007
			130.50	132.00	D911108	1.50	0.008		0.008
			132.00	133.50	D911109	1.50	0.006		0.006
			133.50	135.00	D911111	1.50	<0.005		0.001
			135.00	136.50	D911112	1.50	0.010		0.010
			136.50	138.00	D911113	1.50	0.579		0.579
137.10	137.90	BRE <b>Breccia</b> Breccia. Graywacke fragments in a black graphitic matrix.	138.00	139.50	D911114	1.50	0.120		0.120
			139.50	141.00	D911115	1.50	<0.005		0.001
			141.00	142.50	D911116	1.50	<0.005		0.001
140.70	144.00	Sil <b>Silicification</b> Loc light silicification.	142.50	144.00	D911117	1.50	<0.005		0.001
			144.00	145.50	D911118	1.50	<0.005		0.001
			145.50	147.00	D911119	1.50	<0.005		0.001
			147.00	148.50	D911121	1.50	<0.005		0.001
			148.50	150.00	D911122	1.50	<0.005		0.001
			150.00	151.50	D911123	1.50	<0.005		0.001
			151.50	153.00	D911124	1.50	0.007		0.007
151.50	151.65	BRE <b>Breccia</b> Breccia. Graywacke fragments in a black graphitic matrix.	153.00	154.50	D911125	1.50	<0.005		0.001
			154.50	156.00	D911126	1.50	<0.005		0.001
			156.00	157.50	D911127	1.50	<0.005		0.001
154.60	155.90	GP <b>Graphite</b> Graphitic argillite.	157.50	159.00	D911128	1.50	<0.005		0.001
			159.00	160.50	D911129	1.50	<0.005		0.001
			160.50	162.00	D911131	1.50	<0.005		0.001
			162.00	163.50	D911132	1.50	<0.005		0.001
			163.50	165.00	D911133	1.50	<0.005		0.001
			165.00	166.50	D911134	1.50	<0.005		0.001
			166.50	168.00	D911135	1.50	<0.005		0.001
165.40	165.70	BRE <b>Breccia</b> Breccia. Graywacke fragments in a black graphitic matrix.	168.00	169.50	D911136	1.50	<0.005		0.001
			169.50	171.00	D911137	1.50	<0.005		0.001
			171.00	172.50	D911138	1.50	<0.005		0.001
			172.50	174.00	D911139	1.50	<0.005		0.001
			174.00	175.50	D911141	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
183.80	184.20	BRE <b>Breccia</b> Breccia. Graywacke fragments in a black graphitic matrix.	175.50	177.00	D911142	1.50	<0.005		0.001
			177.00	178.50	D911143	1.50	<0.005		0.001
			178.50	180.00	D911144	1.50	<0.005		0.001
			180.00	181.50	D911146	1.50	<0.005		0.001
			181.50	183.00	D911147	1.50	<0.005		0.001
			183.00	184.50	D911148	1.50	<0.005		0.001
			184.50	186.00	D911149	1.50	<0.005		0.001
			186.00	187.50	D911151	1.50	<0.005		0.001
			187.50	189.00	D911152	1.50	<0.005		0.001
			189.00	190.00	D911153	1.00	<0.005		0.001
			190.00	191.00	D911154	1.00	<0.005		0.001
			191.00	192.00	P009127	1.00	0.009		0.009
			192.00	193.00	P009128	1.00	<0.005		0.001
			193.00	194.00	D911155	1.00	0.006		0.006
			194.00	195.00	D911156	1.00	<0.005		0.001
			195.00	196.50	D911157	1.50	0.005		0.005
			196.50	198.00	D911158	1.50	0.008		0.008
			198.00	199.50	D911159	1.50	<0.005		0.001
			199.50	201.00	D911161	1.50	<0.005		0.001
203.60	213.55	I2 <b>Intermediate Intrusive</b> Medium grained, massive, grey-green colour, some sediment interbedded as well. White feldspar flecks coupled with mm sized grey silica grains. Common qtz veins up to 5cm thick. Sharp irregular upper and lower contacts.	201.00	202.50	D911162	1.50	0.005		0.005
			202.50	204.00	D911163	1.50	0.005		0.005
			204.00	205.50	D911164	1.50	<0.005		0.001
			205.50	207.00	D911165	1.50	<0.005		0.001
			207.00	208.50	D911166	1.50	<0.005		0.001
			208.50	210.00	D911167	1.50	0.008		0.008
			210.00	211.50	D911168	1.50	<0.005		0.001
			211.50	213.00	D911169	1.50	<0.005		0.001
			213.00	214.50	D911171	1.50	0.005		0.005
			214.50	216.00	D911172	1.50	0.006		0.006
			216.00	217.50	D911173	1.50	<0.005		0.001
			217.50	219.00	D911174	1.50	<0.005		0.001
			219.00	220.00	D911175	1.00	<0.005		0.001
220.00	221.00	P009129	1.00	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	221.00	222.00	P009130	1.00	<0.005		0.001
	222.00	223.50	D911176	1.50	<0.005		0.001
	223.50	225.00	D911177	1.50	<0.005		0.001
225.00    Fin du sondage Nombre d'échantillons : 176 Nombre d'échantillons QAQC : 13 Longueur totale échantillonnée : 209.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
26.20	26.20	P009039	O54Pa	0.00	2.290	2.290
47.00	47.00	P009061	O52Pb	0.00	0.318	0.318
86.00	86.00	P009102	O53Pb	0.00	0.626	0.626
102.00	102.00	P009119	O52Pb	0.00	0.327	0.327
112.00	113.00	D911100	D911099	1.00	<0.005	0.001
132.00	132.00	D911110	O52Pb	0.00	0.309	0.309
145.50	147.00	D911120	D911119	1.50	<0.005	0.001
159.00	159.00	D911130	O53Pb	0.00	0.618	0.618
172.50	174.00	D911140	D911139	1.50	<0.005	0.001
178.50	178.50	D911145	m	0.00	<0.005	0.001
184.50	184.50	D911150	O54Pa	0.00	2.100	2.100
198.00	199.50	D911160	D911159	1.50	0.005	0.005
211.50	211.50	D911170	O52Pb	0.00	0.320	0.320



## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-57

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine

Foré par : Multi Drill

Lot :

Décrit par : Dominic Fleming

Du : 2009-05-16

Date de description : 2009-05-23

Au : 2009-05-19

Collet

Azimut : 342.44°  
Plongée : -59.40°  
Longueur : 219.00 m

UTM

Est	629 974.4
Nord	5 374 324.8
Élévation	282.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	342.44°	-60.17°	Non
Reflex	5.00	342.22°	-59.99°	Non
Reflex	10.00	341.98°	-59.92°	Non
Reflex	15.00	341.94°	-59.89°	Non
Reflex	20.00	342.02°	-59.87°	Non
Reflex	25.00	342.03°	-59.83°	Non
Reflex	30.00	342.17°	-59.77°	Non
Reflex	35.00	342.22°	-59.74°	Non
Reflex	40.00	342.24°	-59.70°	Non
Reflex	45.00	342.30°	-59.68°	Non
Reflex	50.00	342.29°	-59.67°	Non
Reflex	55.00	342.31°	-59.65°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	60.00	342.38°	-59.60°	Non
Reflex	65.00	342.52°	-59.57°	Non
Reflex	70.00	342.46°	-59.50°	Non
Reflex	75.00	342.40°	-59.43°	Non
Reflex	80.00	342.45°	-59.33°	Non
Reflex	85.00	342.44°	-59.28°	Non
Reflex	90.00	342.50°	-59.25°	Non
Reflex	95.00	342.53°	-59.20°	Non
Reflex	100.00	342.55°	-59.17°	Non
Reflex	105.00	342.51°	-59.11°	Non
Reflex	110.00	342.53°	-59.08°	Non
Reflex	115.00	342.53°	-58.99°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Surveyed in Nov 2009 by Descarreaux.

Resampled in September 2010 by C. Gagnier.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	11.60	MT <b>Overburden</b> Driller's note: casing at 12m.							
11.60	99.40	SY POR; POR <b>Syenite Porphyry Intrusive; Porphyric</b> Dark-red-green to purple. 40% euhedrals Fld phenos (2-4mm), medium CL, ALB and potassic alteration. Locally less than 40%, around 20% (lower than 55m). Overall groundmass alteration is medium CL, medium potassic, weak CARB, weak SI, pervasive medium SR and patches of weathering alteration (rust).  Fine to medium grains. Foliation 30-40 TCA. 1-2% of micro-fractures filled with silica-carbonate fluid, pervasive ALB of the veinlets.  Locally brecciated, less than 4cm.  Trace to no mineralization. Some patches of mineralization with 3-5% Py, disseminated and in stringers. From 81m to 99.4m, 3-15% disseminated and in stringers. VG specks in quartz vein at 94.1m.  Mag +++  Sharp lower contact at 65 TCA.	11.60	13.80	D506070	2.20	<0.005		0.001
12.00	54.40	FOL <b>Foliation 40°</b> fol 30-40 TCA	13.80	15.00	D506071	1.20	<0.005		0.001
			15.00	16.50	D506072	1.50	0.017		0.017
			16.50	18.10	D506073	1.60	<0.005		0.001
			18.10	19.10	P009256	1.00	<0.005		0.001
19.10	23.10	Chl60; Pot40; Hem10; Wea20 <b>Chloritisation 60; Potassic alteration 40; Hematisation 10; Weathering (Incl. Saproplitic alter.) 20</b> strong alterations	19.10	20.00	P009257	0.90	0.008		0.008
			20.00	21.00	P009258	1.00	0.023		0.023
20.15	20.50	VEI;5;QzCb;T;70°; <b>Vein 5 Quartz Carbonate Tension 70°</b> qtz-carbonate vein	21.00	22.10	P009259	1.10	<0.005		0.001
			22.10	23.10	P009260	1.00	0.069		0.069
			23.10	24.00	D506074	0.90	<0.005		0.001
			24.00	25.00	D506076	1.00	0.065		0.065
			25.00	26.00	P009261	1.00	0.107		0.107
			26.00	26.50	P009262	0.50	0.041		0.041
			26.50	27.50	P009263	1.00	0.084		0.084

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			27.50	28.50	D506078	1.00		0.014		0.014
			28.50	30.00	D506079	1.50		0.008		0.008
			30.00	31.50	D506081	1.50		0.027		0.027
			31.50	33.00	D506082	1.50		0.102		0.102
			33.00	34.50	D506083	1.50		0.230		0.230
			34.50	36.00	D506084	1.50		0.082		0.082
			36.00	37.50	D506085	1.50		0.273		0.273
			37.50	39.00	D506086	1.50		0.522		0.522
			39.00	40.50	D506087	1.50		0.896		0.896
			40.50	42.00	D506088	1.50		0.709		0.709
			42.00	43.40	D506089	1.40		0.317		0.317
			43.40	44.80	D506090	1.40		0.017		0.017
			44.80	45.80	P009265	1.00		0.005		0.005
45.70	46.70	Ser60; Epi20; Chl40	45.80	46.70	P009266	0.90		0.300		0.300
		<b>Sericitisation 60; Epidotisation 20; Chloritisation 40</b>	46.70	47.60	P009267	0.90		0.017		0.017
		Strong alt	47.60	49.40	D506091	1.80		0.488		0.488
			49.40	51.00	D506092	1.60		0.370		0.370
			51.00	52.50	D506093	1.50		0.048		0.048
			52.50	54.00	D506094	1.50		0.033		0.033
			54.00	55.00	P009268	1.00		0.057		0.057
54.40	54.80	FRC	55.00	56.00	P009269	1.00		0.086		0.086
		<b>Fractured 10°</b>								
		fracture								
55.40	56.60	Epi50; Chl60; Ser40	56.00	57.00	P009270	1.00		0.092		0.092
		<b>Epidotisation 50; Chloritisation 60; Sericitisation 40</b>	57.00	58.00	P009271	1.00		0.191		0.191
		strong alterations	58.00	59.00	P009272	1.00		<0.005		0.001
59.00	80.00	Py0.5; Py01	59.00	59.60	P009273	0.60		0.008		0.008
		<b>Pyrite 0.5%; Pyrite 01%</b>	59.60	60.60	P009274	1.00		0.009		0.009
		MNZD with 0.5 to 1% disseminated Py overall, especially around the small breccias.	60.60	61.40	P009309	0.80		0.006		0.006
			61.40	63.00	D506096	1.60		0.006		0.006
62.80	63.30	FRC	63.00	64.50	D506098	1.50		1.480		1.480
		<b>Fractured</b>	64.50	66.00	D506099	1.50		0.224		0.224
		fractured and broken core	66.00	67.50	D506100	1.50		0.048		0.048

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
70.55	70.63	B <b>Breccia</b> Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py.	67.50	69.00	D506101	1.50	0.078		0.078
			69.00	70.00	P009275	1.00	0.430		0.430
			70.00	71.00	P009276	1.00	0.316		0.316
70.90	71.05	B <b>Breccia</b> Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py.	71.00	72.00	P009277	1.00	0.385		0.385
			72.00	73.00	P009278	1.00	2.540		2.540
			73.00	74.00	P009279	1.00	2.410		2.410
73.80	74.00	B <b>Breccia</b> Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py.	74.00	75.00	P009280	1.00	1.260		1.260
			75.00	76.00	P009281	1.00	0.242		0.242
			76.00	77.00	P009282	1.00	0.812		0.812
76.15	76.23	B <b>Breccia</b> Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py.	77.00	78.00	P009283	1.00	1.900		1.900
77.10	77.16	B <b>Breccia</b> Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py.	78.00	79.00	P009284	1.00	0.613		0.613
			79.00	80.00	P009285	1.00	1.185		1.185
79.50	79.60	B <b>Breccia</b>	80.00	81.00	P009286	1.00	0.534		0.534

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
81.00	99.40	Breccia. Gray. Medium to strong silicification, medium albitisation and medium potassic. 50-60% Fld phenos (2-4mm).  Matrix silica and carbonate. 2-5% stringers and disseminated Py. Py03; Py15; Au0.01 <b>Pyrite 03%; Pyrite 15%; Gold 0.01%</b> Py disseminated and in stringers, 3 to 15%  VG specks at 94.1m in a quartz vein	81.00	82.00	P009288	1.00	0.940		0.940
			82.00	83.00	P009289	1.00	0.499		0.499
			83.00	84.00	P009290	1.00	0.211		0.211
			84.00	85.00	P009291	1.00	2.010		2.010
			85.00	86.00	P009292	1.00	0.500		0.500
			86.00	87.00	P009293	1.00	1.545		1.545
			87.00	88.00	P009294	1.00	0.726		0.726
			88.00	89.00	P009295	1.00	0.445		0.445
			89.00	90.00	P009296	1.00	1.110		1.110
			90.00	91.00	P009297	1.00	2.060		2.060
			91.00	92.00	P009298	1.00	1.450		1.450
			92.00	93.00	P009299	1.00	0.527		0.527
			93.00	94.00	P009300	1.00	0.043		0.043
			94.00	95.00	P009301	1.00	0.924		0.924
94.10	94.13	VEI:3;Qz;T;60°;Au01; <b>Vein 3 Quartz Tension 60° Gold01</b> VG specks in qtz vein	95.00	96.00	P009302	1.00	0.038		0.038
			96.00	97.00	P009303	1.00	0.600		0.600
			97.00	98.00	P009304	1.00	1.650		1.650
			98.00	99.00	P009305	1.00	2.320		2.320
			99.00	99.40	P009307	0.40	2.080		2.080
			99.40	119.10	MS; O <b>Mudrock 40°; Laminated</b> Sharp upper contact at 40 TCA. Black to dark-green-black. Aphanitic. Locally moderately carbonated. Highly fractured, well laminated 20-40 TCA. Lightly schistose. 5% fractures filled with silica and calcite. Not magnetic. Sharp lower contact at 30 TCA.  50% of the core is fractured and broken.  Clusters (2-3%) elongated in schistosity.  Trace of Py in stringers in schistosity. Mag +.				

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
99.40	120.00	FAI; FRC; SCH <b>Fault 30°; Fractured; Schistosed</b> 50% of the core is fractured and broken.	99.40	99.90	P009308	0.50	0.239		0.239	
			99.90	101.00	D506102	1.10	0.018		0.018	
			101.00	102.00	D506103	1.00	0.016		0.016	
			102.00	103.50	D506104	1.50	0.011		0.011	
			103.50	105.00	D506105	1.50	0.006		0.006	
			105.00	106.50	D506106	1.50	0.006		0.006	
			106.50	108.00	D506107	1.50	0.014		0.014	
			108.00	109.50	D506108	1.50	0.005		0.005	
			109.50	111.00	D506109	1.50	0.006		0.006	
			111.00	112.50	D506110	1.50	0.006		0.006	
			112.50	114.00	D506111	1.50	<0.005		0.001	
			114.00	115.70	D506112	1.70	0.007		0.007	
			115.70	117.40	D506113	1.70	<0.005		0.001	
			117.40	119.10	D506114	1.70	0.013		0.013	
119.10	120.20	D506116	1.10	<0.005		0.001				
119.10	190.20	S1 <b>Sandstone</b> Sharp upper contact at 30 TCA. Gray-green to yellow-green-gray. Well developed lamination 30-40 TCA. Fine to medium grains elongated in lamination. Matrix silica and carbonate but mostly carbonate. Up to 3% of 0.5-1mm beige leucoxene. Not magnetic.  Strong SR alteration. Locally weakly bleached. Small breccia intervals.  Trace to no mineralization. Some patches (0.01% of groundmass) of massive Py and massive Pyrrhothite.. Low mag.  Locally magnetic. The grain size decreases toward the LC.  1-2% of calcites veinlets and stockworks 1mm-8mm. Weak EPI and CHL of the veinlets.  Lower contact sharp 30 TCA								
120.00	125.50		SCH	120.20	121.50	D506118	1.30	<0.005		0.001
			<b>Schistosed 30°</b>	121.50	123.00	D506119	1.50	<0.005		0.001
			well schisto	123.00	124.50	D506120	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			124.50	126.00	D506121	1.50		0.006
125.50	126.50	FRC <b>Fractured</b> fractured and broken core	126.00	127.50	D506122	1.50		<0.005
			127.50	129.00	D506123	1.50		0.005
127.00	212.00	FOL <b>Foliation 35°</b> foliation 30-40 TCA	129.00	130.50	D506124	1.50		<0.005
			130.50	132.00	D506125	1.50		<0.005
			132.00	133.50	D506126	1.50		<0.005
			133.50	135.00	D506127	1.50		<0.005
			135.00	136.50	D506128	1.50		<0.005
			136.50	138.00	D506129	1.50		<0.005
			138.00	139.50	D506130	1.50		<0.005
			139.50	141.00	D506131	1.50		<0.005
			141.00	142.50	D506132	1.50		<0.005
			142.50	144.00	D506133	1.50		<0.005
			144.00	145.50	D506134	1.50		<0.005
			145.50	147.00	D506136	1.50		<0.005
			147.00	148.50	D506138	1.50		<0.005
			148.50	150.00	D506139	1.50		<0.005
149.90	149.94	VEI;3;Qz;T;70°; <b>Vein 3 Quartz Tension 70°</b> qtz vein	150.00	151.50	D506141	1.50		<0.005
			151.50	153.00	D506142	1.50		<0.005
			153.00	154.50	D506143	1.50		<0.005
			154.50	156.00	D506144	1.50		<0.005
			156.00	157.00	D506145	1.00		<0.005
			157.00	158.00	P009310	1.00		<0.005
157.80	158.30	B <b>Breccia</b> Breccia. Light-green-white. 30% sandstone phenos (5-20mm).  Matrix is carbonate. No mineralization.						
		Upper contact 30 TCA and lower contact 60 TCA						
157.80	165.00	ChI30; Sil40 <b>Chloritisation 30; Silicification 40</b> Strong alt.	158.00	159.00	P009311	1.00		<0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
158.90	159.90	B <b>Breccia</b> Breccia. Light-green-white. 40% sandstone phenos (2-5mm).  Matrix is carbonate. No mineralization.  Upper contact 60 TCA and lower contact 40 TCA	159.00	160.00	P009312	1.00	<0.005		0.001
			160.00	161.00	P009313	1.00	0.006		0.006
			161.00	162.00	P009314	1.00	0.008		0.008
			162.00	163.00	P009315	1.00	0.009		0.009
			163.00	164.00	P009316	1.00	<0.005		0.001
			164.00	165.00	P009317	1.00	0.008		0.008
			164.75	178.00	B <b>Breccia</b> Breccia. Light-green-white. 15% sandstone phenos (2-5mm).  Matrix is carbonate. 3-5% Pyrrhothite massive and 2-3% Py massive.,.  Upper contact 35 TCA and lower contact 60 TCA				
165.00	190.20	Ch140 <b>Chloritisation 40</b> strong CHL	165.00	166.00	P009318	1.00	0.006		0.006
			166.00	167.00	D506146	1.00	<0.005		0.001
			167.00	168.00	D506147	1.00	0.005		0.005
			168.00	169.50	D506148	1.50	0.006		0.006
168.25	168.29	VEI;4;Cc;T;50°;Py02; <b>Vein 4 Calcite Tension 50° Pyrite02</b> 2% Py in calcite vein	169.50	171.00	D506149	1.50	0.006		0.006
			171.00	172.50	D506150	1.50	0.008		0.008
			172.50	174.00	D506151	1.50	0.013		0.013
			174.00	175.50	D506152	1.50	0.009		0.009
			175.50	177.00	D506153	1.50	0.009		0.009
			177.00	178.50	D506154	1.50	0.014		0.014
			178.50	180.00	D506156	1.50	0.012		0.012
178.90	178.96	VEI;6;CcQz;T;70°;Py0.01; <b>Vein 6 Calcite Quartz Tension 70° Pyrite0.</b> calcite-qtz vein							
179.00	179.02	VEI;2;Cc;T;70°;; <b>Vein 2 Calcite Tension 70°</b> calcite vein	180.00	181.50	D506158	1.50	<0.005		0.001
			181.50	183.00	D506159	1.50	<0.005		0.001
			183.00	184.50	D506160	1.50	0.005		0.005
			184.50	186.00	D506161	1.50	<0.005		0.001
			186.00	187.50	D506162	1.50	<0.005		0.001
			187.50	189.00	D506163	1.50	<0.005		0.001
			189.00	190.20	D506164	1.20	0.005		0.005



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
190.20	219.00	S; FIN <b>Sediment (Meta incl.); Fine grains</b> Light to medium gray metasediment. Matrix is submm. Foliation is consistent at 30-35TCA, fragments are along foliation. Matrix is submm.  Alterations : medium CHL, medium SR, weak ALB  10% of quartz vein submm to 11cm. 2-3 of micro-fractures filled by silica-carbonate fluids.  No mineralization to tr of disseminated PY.  Upper contact sharp at 30TCA.							
190.20	219.00	Chl40; Alb10; Ser10 <b>Chloritisation 40; Albitisation 10; Sericitisation 10</b> Strong alterations	190.20	191.80	D506165	1.60	<0.005		0.001
			191.80	193.50	D506166	1.70	<0.005		0.001
192.90	192.95	VEI;5;CcQz;T;40°; <b>Vein 5 Calcite Quartz Tension 40°</b> qtz-calcite vein							
193.25	193.29	VEI;4;CcQz;T;70°; <b>Vein 4 Calcite Quartz Tension 70°</b> qtz-calcite vein							
193.40	193.46	VEI;6;CcQz;T;60°; <b>Vein 6 Calcite Quartz Tension 60°</b> qtz-calcite vein	193.50	195.00	D506167	1.50	<0.005		0.001
194.45	194.51	VEI;6;CcQz;T;70°; <b>Vein 6 Calcite Quartz Tension 70°</b> qtz-calcite vein	195.00	196.50	D506168	1.50	<0.005		0.001
195.15	195.60	VEI;45;CcQz;T;;; <b>Vein 45 Calcite Quartz Tension</b> qtz-calcite vein	196.50	198.00	D506169	1.50	<0.005		0.001
			198.00	199.50	D506170	1.50	<0.005		0.001
199.45	199.55	VEI;10;Qz;T;60°; <b>Vein 10 Quartz Tension 60°</b> qtz vein	199.50	201.00	D506171	1.50	<0.005		0.001
200.40	200.45	VEI;5;CcQz;T;;; <b>Vein 5 Calcite Quartz Tension</b> qtz-calcite vein	201.00	202.50	D506172	1.50	<0.005		0.001
202.50	202.65	VEI;15;CcQz;T;60°; <b>Vein 15 Calcite Quartz Tension 60°</b>	202.50	204.00	D506173	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		qtz-calcite vein	204.00	205.50	D506174	1.50	<0.005		0.001
			205.50	207.00	D506176	1.50	<0.005		0.001
			207.00	208.50	D506178	1.50	<0.005		0.001
			208.50	210.00	D506179	1.50	<0.005		0.001
			210.00	211.50	D506181	1.50	<0.005		0.001
			211.50	213.00	D506182	1.50	<0.005		0.001
212.10	212.17	VEI;7;CcQz;T;40°;; <b>Vein 7 Calcite Quartz Tension 40°</b>							
		qtz-calcite vein							
212.90	213.00	VEI;;CcQz;T;40°;; <b>Vein Calcite Quartz Tension 40°</b>	213.00	214.50	D506183	1.50	<0.005		0.001
		qtz-calcite vein							
213.75	213.88	VEI;13;Qz;T;60°;; <b>Vein 13 Quartz Tension 60°</b>							
		qtz vein							
214.40	214.44	VEI;4;CcQz;T;40°;; <b>Vein 4 Calcite Quartz Tension 40°</b>	214.50	216.00	D506184	1.50	<0.005		0.001
		qtz-calcite vein							
214.60	214.75	VEI;15;CcQz;T;40°;; <b>Vein 15 Calcite Quartz Tension 40°</b>	216.00	217.50	D506185	1.50	<0.005		0.001
		qtz-calcite vein	217.50	219.00	D506186	1.50	<0.005		0.001
219.00	Fin du sondage								
	Nombre d'échantillons : 162								
	Nombre d'échantillons QAQC : 18								
	Longueur totale échantillonnée : 207.40								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
24.00	25.00	D506077	D506076	1.00	0.116	0.116
24.00	24.00	D506075	O54Pa	0.00	2.810	2.810
27.50	27.50	P009264	O52Pb	0.00	0.323	0.323
30.00	30.00	D506080	m	0.00	<0.005	0.001
54.00	54.00	D506095	O61d	0.00	4.900	4.900
61.40	63.00	D506097	D506096	1.60	<0.005	0.001
81.00	81.00	P009287	O54Pa	0.00	2.900	2.900
99.00	99.00	P009306	O53Pb	0.00	0.651	0.651
119.10	120.20	D506117	D506116	1.10	<0.005	0.001
119.10	119.10	D506115	O52Pb	0.00	0.314	0.314
145.50	145.50	D506135	O53Pb	0.00	0.605	0.605
145.50	147.00	D506137	D506136	1.50	<0.005	0.001
150.00	150.00	D506140	m	0.00	<0.005	0.001
178.50	178.50	D506155	O54Pa	0.00	2.910	2.910
178.50	180.00	D506157	D506156	1.50	0.010	0.010
205.50	205.50	D506175	O61d	0.00	4.890	4.890
205.50	207.00	D506177	D506176	1.50	<0.005	0.001
210.00	210.00	D506180	m	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-58	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multi drill	Lot :	
Décrit par : Geneviève Carignan	Du : 2009-05-29	Date de description : 2009-06-02
	Au : 2009-06-02	

Collet

Azimut : 0.00°  
 Plongée : -89.40°  
 Longueur : 240.00 m

UTM

Est	630 007.3
Nord	5 374 348.7
Élévation	283.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	349.65°	-88.70°	Non
Reflex	63.00	350.95°	-89.40°	Non
Reflex	90.00	359.95°	-88.50°	Non
Reflex	120.00	2.65°	-88.90°	Non
Reflex	150.00	13.75°	-88.60°	Non
Reflex	180.00	76.05°	-89.70°	Oui
Reflex	210.00	343.75°	-89.20°	Oui
Reflex	240.00	6.85°	-89.90°	Oui

Type	Profondeur	Azimut	Plongée	Invalide

Description

NAD 83, UTM Zone 17  
 Surveyed in Nov 2009 by Descarreaux.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	6.00	MT <b>Casing</b> Casing.							
6.00	115.10	SY POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Grey-purple-greenish aphanitic to fine grained matrix with 20-25% Fp phenos (smaller than 2cm and loc zoned with a white contour). Massive (foliated @ 60° TCA when moderate chloritisation) and magnetic. Loc brecciated. Homogenous.  1-2% white Qz veins @ 45-55° TCA.  Light to loc moderate chloritisation and loc light carbonatisation. Weathering in fractures until 60m.  Tr-1% very fine disseminated pyrite.  **Local foliation caused by weak shearing	6.00	7.50	D911178	1.50	0.007		0.007
			7.50	9.00	D911179	1.50	0.010		0.010
			9.00	10.50	D911181	1.50	0.208		0.208
			10.50	12.00	D911182	1.50	0.007		0.007
			12.00	13.50	D911183	1.50	0.008		0.008
			13.50	15.00	D911184	1.50	0.020		0.020
			15.00	16.50	D911186	1.50	0.011		0.011
			16.50	18.00	D911187	1.50	0.053		0.053
			18.00	19.50	D911188	1.50	0.006		0.006
			19.50	21.00	D911189	1.50	<0.005		0.001
			21.00	22.50	D911191	1.50	0.005		0.005
			22.50	24.00	D911192	1.50	0.007		0.007
			24.00	25.50	D911193	1.50	0.014		0.014
			25.50	27.00	D911194	1.50	0.009		0.009
			27.00	28.00	D911195	1.00	<0.005		0.001
			28.00	29.00	P008732	1.00	<0.005		0.001
28.30	34.00	Sil <b>Silicification</b> Light to moderate silicification. Pervasive and in veinlets @ 50-60° TCA.							
28.30	34.00	Py01 <b>Pyrite 01%</b> 1-2% very fine disseminated pyrite.	29.00	30.00	P008733	1.00	0.011		0.011
			30.00	31.00	P008734	1.00	0.007		0.007
			31.00	32.00	P008735	1.00	<0.005		0.001
			32.00	33.00	P008736	1.00	0.005		0.005
			33.00	34.00	P008737	1.00	<0.005		0.001
			34.00	35.00	P008738	1.00	<0.005		0.001
			35.00	36.00	P008739	1.00	<0.005		0.001
			36.00	37.00	P008741	1.00	0.335		0.335
			37.00	38.00	P008742	1.00	0.580		0.580
37.70	38.10	Py02 <b>Pyrite 02%</b> 2% very fine disseminated in a siliceous syenite.	38.00	39.00	P008743	1.00	1.075		1.075
			39.00	40.00	P008744	1.00	0.185		0.185

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			40.00	41.00	P008745	1.00		0.008		0.008
			41.00	42.00	P008746	1.00		<0.005		0.001
			42.00	43.00	P008747	1.00		<0.005		0.001
			43.00	44.00	P008748	1.00		0.005		0.005
			44.00	45.00	P008749	1.00		0.006		0.006
			45.00	46.00	P008750	1.00		<0.005		0.001
			46.00	47.00	P008751	1.00		<0.005		0.001
			47.00	48.00	P008752	1.00		<0.005		0.001
			48.00	49.00	P008753	1.00		<0.005		0.001
			49.00	50.00	P008754	1.00		0.041		0.041
			50.00	51.00	P008755	1.00		0.055		0.055
51.00	51.30	Py03 <b>Pyrite 03%</b> 2-3% very fine disseminated pyrite.	51.00	52.00	P008756	1.00		0.013		0.013
			52.00	53.00	P008757	1.00		0.020		0.020
			53.00	54.00	P008758	1.00		<0.005		0.001
			54.00	55.00	P008759	1.00		<0.005		0.001
			55.00	56.00	P008760	1.00		<0.005		0.001
			56.00	57.00	P008761	1.00		<0.005		0.001
			57.00	58.00	P008762	1.00		0.012		0.012
			58.00	59.00	P008763	1.00		<0.005		0.001
59.00	59.30	Py03 <b>Pyrite 03%</b> 1-3% fine to very fine disseminated pyrite (loc cubic).	59.00	60.00	P008764	1.00		0.083		0.083
			60.00	61.00	P008766	1.00		<0.005		0.001
			61.00	62.00	P008767	1.00		0.023		0.023
61.40	61.70	Py02 <b>Pyrite 02%</b> 1-2% very fine disseminated pyrite.	62.00	63.00	D911196	1.00		0.008		0.008
			63.00	64.50	D911197	1.50		0.008		0.008
			64.50	66.00	D911198	1.50		0.009		0.009
			66.00	67.50	D911199	1.50		0.040		0.040
			67.50	69.00	D911201	1.50		<0.005		0.001
			69.00	70.50	D911202	1.50		0.065		0.065
			70.50	72.00	D911203	1.50		0.006		0.006
			72.00	73.50	D911204	1.50		0.006		0.006
			73.50	75.00	D911205	1.50		<0.005		0.001
			75.00	76.50	D911206	1.50		0.082		0.082
75.60	81.95	Alb	76.50	78.00	D911207	1.50		0.013		0.013

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Albitisation</b> Light pervasive albitisation.	78.00	79.00	P008768	1.00	0.017		0.017
78.15	78.60	BRE <b>Breccia</b> **moderately brecciated in a chlorite matrix.							
78.20	78.60	Py02	79.00	80.00	P008769	1.00	0.005		0.005
		<b>Pyrite 02%</b> 1-2% very fine disseminated pyrite in a breccia and the walls.	80.00	81.00	P008770	1.00	0.015		0.015
			81.00	82.00	P008771	1.00	0.037		0.037
81.90	83.20	Py02	82.00	83.00	P008772	1.00	0.280		0.280
		<b>Pyrite 02%</b> 1-2% very fine disseminated pyrite.	83.00	84.00	P008773	1.00	0.359		0.359
			84.00	85.00	P008774	1.00	0.105		0.105
			85.00	86.00	D911208	1.00	0.005		0.005
			86.00	87.00	D911209	1.00	<0.005		0.001
			87.00	88.50	D911211	1.50	<0.005		0.001
			88.50	90.00	D911212	1.50	<0.005		0.001
			90.00	91.50	D911213	1.50	0.031		0.031
			91.50	93.00	D911214	1.50	0.006		0.006
			93.00	94.00	P008775	1.00	0.080		0.080
93.20	93.70	Sil; Chl	94.00	95.00	P008776	1.00	0.011		0.011
		<b>Silicification; Chloritisation</b> Light silicification and chloritisation. Smokey to white Qz veins (<2.0cm) @ 40-50° and 90° TCA. 1% very fine to fine disseminated pyrite.	95.00	96.00	D911215	1.00	0.006		0.006
			96.00	97.50	D911216	1.50	<0.005		0.001
			97.50	99.00	D911217	1.50	0.005		0.005
97.70	97.85	VEI;0;Qz Cc;;; <b>Vein 0 Quartz Calcite</b> smokey qtz-pink calcite vein with some clorite alteration of surrounding rock.	99.00	100.50	D911218	1.50	0.005		0.005
			100.50	102.00	D911219	1.50	<0.005		0.001
			102.00	103.50	D911221	1.50	0.049		0.049
			103.50	105.00	D911222	1.50	0.031		0.031
			105.00	106.00	D911223	1.00	0.007		0.007
			106.00	107.00	P008777	1.00	<0.005		0.001
			107.00	108.00	P008778	1.00	0.006		0.006
			108.00	109.00	P008779	1.00	<0.005		0.001
			109.00	110.00	P008780	1.00	<0.005		0.001
			110.00	111.00	P008781	1.00	<0.005		0.001
			111.00	112.00	P008782	1.00	<0.005		0.001
			112.00	113.00	P008783	1.00	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
115.10	154.80	<p>SY POR</p> <p><b>Syenite Porphyry Intrusive</b></p> <p>Intrusive rock. Green-greyish aphanitic to fine grained matrix with 5% altered Fp phenos (~1cm). Massive and magnetic. Loc brecciated by carbonates injections. Homogenous.</p> <p>1% Qz-Cc veins @ 40-50° TCA.</p> <p>Light pervasive chloritisation and light carbonatation in injections.</p> <p>1% (loc 2%) very fine to fine pyrite. Disseminated and in fine stringers associated with calcite injections.</p> <p>Upper contact is gradual.</p>	113.00	114.00	P008784	1.00	0.006		0.006
			114.00	115.00	P008785	1.00	<0.005		0.001
			115.00	116.00	P008787	1.00	0.007		0.007
			116.00	117.00	P008788	1.00	0.009		0.009
			117.00	118.00	P008789	1.00	0.021		0.021
			118.00	119.00	P008790	1.00	0.016		0.016
			119.00	120.00	P008791	1.00	0.011		0.011
			120.00	121.00	P008792	1.00	0.011		0.011
			121.00	122.00	P008793	1.00	<0.005		0.001
			122.00	123.00	P008794	1.00	<0.005		0.001
			123.00	124.00	P008795	1.00	0.008		0.008
			124.00	125.00	P008796	1.00	0.006		0.006
			125.00	126.00	P008797	1.00	<0.005		0.001
			126.00	127.00	P008798	1.00	0.008		0.008
115.10	119.70	<p>Chl; Epi</p> <p><b>Chloritisation; Epidotisation</b></p> <p>Light pervasive epidotisation with stringers of dark green chlorite filling the fractures.</p> <p>118.8-119.2m: high chloritisation with light sericitisation making a foliation @ 40° TCA.</p>							
115.10	119.70	<p>BRE</p> <p><b>Breccia</b></p> <p>Moderately to highly brecciated.</p> <p>Sheared from 118.6 - 119.5m - foliation @ 40 DTCA. Moderate qtz-carb veining also.</p>							
115.10	119.70	<p>Py01</p> <p><b>Pyrite 01%</b></p> <p>1% (loc2%) very fine to fine (loc cubic) disseminated pyrite.</p>							
126.70	132.00	<p>Py02</p> <p><b>Pyrite 02%</b></p> <p>2-3% very fine to fine pyrite. Disseminated and infine stringers mostly associated with calcite injections.</p>	127.00	128.00	P008799	1.00	0.010		0.010
			128.00	129.00	P008800	1.00	0.009		0.009
			129.00	130.00	P008801	1.00	0.006		0.006
			130.00	131.00	P008802	1.00	0.016		0.016
			131.00	132.00	P008803	1.00	0.013		0.013



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
141.00	146.20	Py02 <b>Pyrite 02%</b> 2-3% very fine pyrite. Disseminated and in fine stringers.	132.00	133.00	P008805	1.00	0.010		0.010
			133.00	134.00	P008806	1.00	0.008		0.008
			134.00	135.00	P008807	1.00	0.006		0.006
			135.00	136.00	P008808	1.00	0.006		0.006
			136.00	137.00	P008809	1.00	0.006		0.006
			137.00	138.00	P008810	1.00	0.013		0.013
			138.00	139.00	P008811	1.00	0.008		0.008
			139.00	140.00	P008812	1.00	0.007		0.007
			140.00	141.00	P008813	1.00	0.005		0.005
			141.00	142.00	P008814	1.00	0.005		0.005
			142.00	143.00	P008815	1.00	<0.005		0.001
			143.00	144.00	P008816	1.00	0.012		0.012
			144.00	145.00	P008817	1.00	0.005		0.005
			145.00	146.00	P008818	1.00	<0.005		0.001
			146.00	147.00	P008819	1.00	0.006		0.006
			147.00	148.50	D911224	1.50	<0.005		0.001
			148.50	150.00	D911225	1.50	<0.005		0.001
			150.00	151.50	D911226	1.50	0.005		0.005
			151.50	153.00	D911227	1.50	0.006		0.006
153.00	154.00	P008820	1.00	0.005		0.005			
154.00	155.00	P008821	1.00	0.025		0.025			
153.20	153.40	Sil <b>Silicification</b> Light silicification in veins @ 40-50° TCA.							
154.70	155.00	Ser <b>Sericitisation</b> Light sericitisation in fine laminations.							
154.80	174.30	BA <b>Mafic Meta-Volcanic</b> Volcanic rock ? Dark green to loc pale green aphanitic to fine grained matrix. Moderatly foliated @ 20-40° TCA. Homogenous and non magnetic.  Light to loc moderate chloritisation and carbonatation in injections (@ ~50°TCA) and loc light sericitisation.  Tr-1% fine pyrite (mostly cubic).	155.00	156.00	P008822	1.00	0.016		0.016
			156.00	157.50	D911228	1.50	<0.005		0.001
			157.50	159.00	D911229	1.50	<0.005		0.001
			159.00	160.50	D911231	1.50	<0.005		0.001
			160.50	162.00	D911232	1.50	<0.005		0.001
			162.00	163.50	D911233	1.50	<0.005		0.001
			163.50	165.00	D911234	1.50	0.005		0.005
			165.00	166.50	D911235	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Upper contact @ 65° TCA.	166.50	168.00	D911236	1.50	<0.005		0.001
			168.00	169.50	D911237	1.50	<0.005		0.001
		**intermixing of mafic and intermediate volcanics. Locally dark grey-green with white feldspar flecks, often oriented concordant to foliation. Abundant qtz-calcite veins at varying orientations.	169.50	171.00	D911238	1.50	0.006		0.006
			171.00	172.50	D911239	1.50	0.608		0.608
			172.50	174.00	D911241	1.50	0.007		0.007
			174.00	175.00	D911242	1.00	0.010		0.010
174.30	240.00	S	175.00	176.00	P008824	1.00	2.680		2.680
		<b>Sediment (Meta incl.)</b>	176.00	177.00	P008825	1.00	4.130		4.130
		Graphitic black to pale green aphanitic matrix interbedding with pale grey chert? Loc brecciated.							
		Foliated or bedding @ 40-50° TCA and non magnetic. Fractured mostly in the graphitic argillite.							
		Light carbonatisation.							
		tr-3% fine disseminated (cubic) pyrite, in cclusters and fine stringers.							
		Not parallel with the bedding(?).							
		Upper contact sharp @ 45° TCA.							
		Homogenous. Loc brecciated with a dark chlorite matrix.							
		1% Cc veins @ 40-50° and ~90° TCA.							
		Moderate pervasive bleaching.							
		**change from original log - unit 187.70-240, amalgamated into this unit.							
		Unit is sediments with interbedding of mafic volcanic material, as broken out in litho 2							
		Contains massive sandstone beds up to 7m thick.							
176.10	176.50	FRC	177.00	178.50	D911243	1.50	4.630		4.630
		<b>Fractured</b>							
		Broken core.							
178.30	178.70	FRC	178.50	180.00	D911244	1.50	0.050		0.050
		<b>Fractured</b>							
		Broken core.							
178.80	182.90	V3	180.00	181.50	D911246	1.50	0.005		0.005
		<b>Mafic Meta-Volcanic</b>	181.50	183.00	D911247	1.50	0.014		0.014
		Pale green fine grained matrix. Foliated @ 40° TCA and non magnetic. Homogenous.	183.00	184.00	P008826	1.00	0.045		0.045
		Light carbonatisation in injections and pervasive chloritisation.							
		Tr fine disseminated pyrite.							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
183.90	185.00	Sharp contacts @ 60° TCA. BRE <b>Breccia</b> Siliceous breccia. Sediments fragments in a siliceous-carbonates matrix.						
184.00	184.90	Sil <b>Silicification</b> Light to moderate pervasive silicification.	184.00	185.00	P008827	1.00	0.047	0.047
			185.00	186.00	P008828	1.00	0.026	0.026
			186.00	187.00	P008829	1.00	0.026	0.026
			187.00	188.00	P008830	1.00	0.016	0.016
			188.00	189.00	P008831	1.00	0.009	0.009
			189.00	190.00	P008832	1.00	0.005	0.005
			190.00	191.00	D911248	1.00	0.005	0.005
			191.00	192.00	D911249	1.00	0.005	0.005
			192.00	193.50	D911251	1.50	0.005	0.005
			193.50	195.00	D911252	1.50	<0.005	0.001
			195.00	196.50	D911253	1.50	<0.005	0.001
			196.50	198.00	D911254	1.50	0.006	0.006
			198.00	199.50	D911255	1.50	<0.005	0.001
			199.50	201.00	D911256	1.50	<0.005	0.001
199.85	206.00	BRE <b>Breccia</b> Breccia. Pale green fragments (angular to rounded and 0.3-5cm) in a dark chloritic matrix. Fragments aligned @ 40-50° TCA. 1% fine to medium grained disseminated pyrite.	201.00	202.50	D911257	1.50	0.005	0.005
			202.50	204.00	D911258	1.50	0.007	0.007
			204.00	205.50	D911259	1.50	<0.005	0.001
			205.50	207.00	D911261	1.50	0.009	0.009
			207.00	208.50	D911262	1.50	0.005	0.005
			208.50	210.00	D911263	1.50	<0.005	0.001
			210.00	211.50	D911264	1.50	0.007	0.007
211.10	211.50	BRE <b>Breccia</b> Breccia. Green rounded fragments in a dark chloritic-carbonates matrix. 1-2% fine disseminated pyrite.  Sharp contacts @ 60° TCA.	211.50	213.00	D911265	1.50	0.005	0.005
			213.00	214.00	P008833	1.00	<0.005	0.001
			214.00	215.00	P008834	1.00	<0.005	0.001
			215.00	216.00	P008835	1.00	<0.005	0.001
			216.00	217.50	D911266	1.50	<0.005	0.001
			217.50	219.00	D911267	1.50	<0.005	0.001
			219.00	220.50	D911268	1.50	<0.005	0.001
			220.50	222.00	D911269	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
220.70	220.90	Py <b>Pyrite</b> 2-4% medium grained pyrite and fine pyrite in clusters.	222.00	223.50	D911271	1.50	0.005		0.005
			223.50	225.00	D911272	1.50	<0.005		0.001
			225.00	226.50	D911273	1.50	<0.005		0.001
225.30	225.90	BRE <b>Breccia</b> Breccia. Same as 199.85-206m.  Contacts @ 30° TCA.	226.50	228.00	D911274	1.50	<0.005		0.001
			228.00	229.50	D911275	1.50	<0.005		0.001
			229.50	231.00	D911276	1.50	<0.005		0.001
			231.00	232.50	D911277	1.50	0.005		0.005
			232.50	234.00	D911278	1.50	0.005		0.005
			234.00	235.50	D911279	1.50	<0.005		0.001
			235.50	237.00	D911281	1.50	0.008		0.008
236.50	237.30	BRE <b>Breccia</b> Breccia. Same as 199.85-206m. 2-4% medium grained to fine pyrite. Disseminated and in clusters.  Contacts @ 20° TCA.	237.00	238.50	D911282	1.50	0.005		0.005
			238.50	240.00	D911283	1.50	0.010		0.010
240.00	Fin du sondage Nombre d'échantillons : 192 Nombre d'échantillons QAQC : 18 Longueur totale échantillonnée : 234.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.50	9.00	D911180	D911179	1.50	0.016	0.016
13.50	13.50	D911185	m	0.00	<0.005	0.001
19.50	19.50	D911190	O53Pb	0.00	0.611	0.611
35.00	35.00	P008740	O53Pb	0.00	0.593	0.593
59.00	59.00	P008765	O54Pa	0.00	2.910	2.910
66.00	67.50	D911200	D911199	1.50	0.087	0.087
86.00	86.00	D911210	O54Pa	0.00	2.980	2.980
100.50	102.00	D911220	D911219	1.50	<0.005	0.001
114.00	114.00	P008786	O52Pb	0.00	0.316	0.316
131.00	131.00	P008804	O53Pb	0.00	0.651	0.651
155.00	155.00	P008823	O54Pa	0.00	2.940	2.940
157.50	157.50	D911230	O52Pb	0.00	0.311	0.311
171.00	172.50	D911240	D911239	1.50	0.420	0.420
178.50	178.50	D911245	m	0.00	0.008	0.008
191.00	191.00	D911250	O53Pb	0.00	0.621	0.621
204.00	205.50	D911260	D911259	1.50	0.005	0.005
220.50	220.50	D911270	O54Pa	0.00	2.810	2.810
234.00	235.50	D911280	D911279	1.50	0.006	0.006

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-59	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multidrill	Lot :	
Décrit par : Genevieve Carignan	Du : 2009-05-22	Date de description : 2009-05-27
	Au : 2009-05-30	

Collet

Azimut : 340.50°  
 Plongée : -77.60°  
 Longueur : 240.00 m

UTM

Est	629 974.6
Nord	5 374 324.3
Élévation	282.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	331.75°	-78.60°	Non
Reflex	60.00	334.85°	-78.40°	Non
Reflex	90.00	338.25°	-78.10°	Non
Reflex	126.00	336.85°	-77.90°	Non
Reflex	150.00	336.85°	-77.70°	Non
Reflex	180.00	336.15°	-77.80°	Non
Reflex	210.00	339.85°	-77.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

Resampled by Moustapha Seck 13/09/2018  
 \* from 112 to 114 and 114.5 to 116.2 m core not recovered

NAD 83, UTM Zone 17

Dimension de la carotte : NQ Cimenté : Non Entreposé : Oui

Surveyed in Nov 2009 by Descarreaux.

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	12.30	MT <b>Casing</b>	12.00	13.00	P009131	1.00	0.019		0.019
12.30	113.70	SY POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Grey-purplish fine grained to aphanitic matrix with 3-5% Fp phenos (0.1-0.5cm). Massive and magnetic. Light carbonatisation in injections and light pervasive chloritisation and in dark green stringers. Light weathering in the fractures unntil 50m. Tr white Qz veins @ 60° TCA. Tr very fine disseminated pyrite (loc in fine stringers).	13.00	14.00	P009132	1.00	0.315	3.52	0.315
			14.00	15.00	P009133	1.00	3.630		3.520
			15.00	16.00	P009134	1.00	0.133		0.133
			16.00	17.00	P009135	1.00	0.551		0.551
			17.00	18.00	P009136	1.00	0.314		0.314
			18.00	19.00	P009137	1.00	0.009		0.009
			19.00	20.00	P009138	1.00	0.005		0.005
			20.00	21.00	P009139	1.00	0.022		0.022
			21.00	22.00	P009141	1.00	0.005		0.005
			22.00	23.00	P009142	1.00	<0.005		0.001
			23.00	24.00	P009143	1.00	0.011		0.011
			24.00	25.00	P009144	1.00	0.007		0.007
			25.00	26.00	P009145	1.00	0.006		0.006
			26.00	27.00	P009146	1.00	0.370		0.370
			27.00	28.00	P009147	1.00	0.424		0.424
			28.00	29.00	P009148	1.00	0.206		0.206
			29.00	30.00	P009149	1.00	4.010	3.88	3.880
			30.00	31.00	P009150	1.00	0.331		0.331
			31.00	32.00	P009151	1.00	0.009		0.009
			32.00	33.00	P009152	1.00	0.008		0.008
			33.00	34.00	P009153	1.00	<0.005		0.001
			34.00	35.00	P009154	1.00	0.015		0.015
			35.00	36.00	P009155	1.00	0.009		0.009
			36.00	37.00	P009156	1.00	0.006		0.006
			37.00	38.00	P009157	1.00	0.027		0.027
			38.00	39.00	P009158	1.00	0.025		0.025
			39.00	40.00	P009159	1.00	<0.005		0.001
			40.00	41.00	P009160	1.00	0.005		0.005
40.70	74.90	I2D POR <b>Syenite Porphyry intrusive</b> Same as Main litho, except 1-2% Fp phenos.	41.00	42.00	P009161	1.00	<0.005		0.001
			42.00	43.00	P009163	1.00	0.007		0.007
			43.00	44.00	P009164	1.00	0.013		0.013



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
54.30	71.00	Chl++ <b>Moderate Chloritisation</b>	44.00	45.00	P009165	1.00	0.007		0.007
			45.00	46.00	P009166	1.00	0.014		0.014
			46.00	47.00	P009167	1.00	0.021		0.021
			47.00	48.00	P009168	1.00	0.006		0.006
			48.00	49.00	P009169	1.00	0.005		0.005
			49.00	50.00	P009170	1.00	0.008		0.008
			50.00	51.00	P009171	1.00	0.006		0.006
			51.00	52.00	P009172	1.00	0.005		0.005
			52.00	53.00	P009173	1.00	<0.005		0.001
			53.00	54.00	P009174	1.00	<0.005		0.001
			54.00	55.00	P009175	1.00	0.005		0.005
			55.00	56.00	P009176	1.00	0.006		0.006
			56.00	57.00	P009177	1.00	<0.005		0.001
			57.00	58.00	P009178	1.00	0.005		0.005
			58.00	59.00	P009179	1.00	0.009		0.009
			59.00	60.00	P009181	1.00	0.005		0.005
			63.50	63.60	VEI;1;QzCcCl;90°;Py01; <b>Vein 1 Quartz Calcite Chlorite 90° Pyrite01%</b> 10cm Qz-Cc-Cl vein with irregular contacts and traces of pyrite.	60.00	61.00	P009182	1.00
61.00	62.00	P009183				1.00	<0.005		0.001
62.00	63.00	P009184				1.00	<0.005		0.001
63.00	64.00	P009185				1.00	<0.005		0.001
64.00	65.00	P009186				1.00	<0.005		0.001
65.00	66.00	P009187				1.00	<0.005		0.001
66.00	67.00	P009188				1.00	<0.005		0.001
67.00	68.00	P009189				1.00	<0.005		0.001
68.00	69.00	P009190				1.00	<0.005		0.001
69.00	70.00	P009191				1.00	0.005		0.005
72.25	72.50	Py01 <b>Pyrite 01%</b> 1-2% very fine disseminated pyrite in a siliceous carbonated syenite.	70.00	71.00	P009192	1.00	0.005		0.005
			71.00	72.00	P009193	1.00	<0.005		0.001
			72.00	73.00	P009194	1.00	0.129		0.129
			73.00	74.00	P009195	1.00	0.033		0.033
			74.00	75.00	P009196	1.00	0.034		0.034
			75.00	76.00	P009197	1.00	<0.005		0.001
			76.00	77.00	P009198	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			77.00	78.00	P009199	1.00		0.350		0.350
			78.00	79.00	P009200	1.00		0.012		0.012
			79.00	80.00	P009202	1.00		0.005		0.005
			80.00	81.00	P009203	1.00		0.097		0.097
			81.00	82.00	P009204	1.00		0.045		0.045
			82.00	83.00	P009205	1.00		0.017		0.017
			83.00	84.00	P009206	1.00		0.013		0.013
83.35	114.00	Epi <b>Epidotisation</b> Light to loc moderate pervasive epidotisation (matrix and Fp).								
83.70	84.30	Py02 <b>Pyrite 02%</b> 1-2% disseminated fine cubic pyrite.	84.00	85.00	P009207	1.00		0.055		0.055
			85.00	86.00	P009208	1.00		0.026		0.026
			86.00	87.00	P009209	1.00		<0.005		0.001
			87.00	88.00	P009210	1.00		0.014		0.014
87.20	87.90	Py01 <b>Pyrite 01%</b> 1-2% very fine disseminated pyrite.	88.00	89.00	P009211	1.00		0.134		0.134
			89.00	90.00	P009212	1.00		1.005		1.005
			90.00	91.00	P009213	1.00		0.163		0.163
			91.00	92.00	P009214	1.00		0.008		0.008
			92.00	93.00	P009215	1.00		0.010		0.010
			93.00	94.00	P009216	1.00		0.006		0.006
			94.00	95.00	P009217	1.00		0.059		0.059
			95.00	96.00	P009218	1.00		0.018		0.018
			96.00	97.00	P009219	1.00		<0.005		0.001
			97.00	98.00	P009220	1.00		<0.005		0.001
			98.00	99.00	P009221	1.00		0.033		0.033
99.00	99.10	VEI; QzCcCl; 65°; Py0.5; <b>Vein Quartz Calcite Chlorite 65° Pyrite 0.5%</b> 10 cm Qz-Cc-Cl vein with traces of pyrite.	99.00	100.00	P009222	1.00		0.187		0.187
100.00	114.00	Py01 <b>Pyrite 01%</b> 1-2% very fine disseminated pyrite.	100.00	101.00	P009223	1.00		0.031		0.031
			101.00	102.00	P009225	1.00		0.037		0.037
			102.00	103.00	P009226	1.00		0.122		0.122
			103.00	104.00	P009227	1.00		0.006		0.006
			104.00	105.00	P009228	1.00		0.013		0.013
			105.00	106.00	P009229	1.00		0.010		0.010

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
113.70	240.00	<p>S</p> <p><b>Sediment (Meta incl.)</b></p> <p>Interbedding of greywacke/chert/graphitic argillite. Pale green to grey (to black for the graphitic argillite) aphanitic to fine grained matrix. Light foliation @ 30° and non magnetic. Loc brecciated.</p> <p>Light to loc moderate carbonatisation in injections and veins @ 40°. Loc light sericitisation and loc silicification.</p> <p>1% very fine disseminated pyrite.</p> <p>Upper contact sharp but broken.</p>	106.00	107.00	P009230	1.00	<0.005		0.001
			107.00	108.00	P009231	1.00	0.021		0.021
			108.00	109.00	P009232	1.00	0.009		0.009
			109.00	110.00	P009233	1.00	0.023		0.023
			110.00	111.00	P009234	1.00	0.589		0.589
			111.00	112.00	P009235	1.00	0.663		0.663
113.70	116.90	<p>S10</p> <p><b>Chert</b></p> <p>Grey very hard aphanitic matrix. Massive or laminated @ ~90° TCA. Non magnetic.</p> <p>Light carbonatisation.</p> <p>2-3% very fine to fine pyrite. Disseminated and in small veinlets.</p> <p>Contacts are sharp but broken.</p>	114.00	114.50	P009236	0.50	0.576		0.576
			116.20	117.00	P009237	0.80	0.049		0.049
116.90	119.70	<p>Sil; Alb</p> <p><b>Silicification; Albitisation</b></p> <p>Light to moderate silicification and light albitisation.</p>							
116.90	121.10	<p>Py03</p> <p><b>Pyrite 03%</b></p> <p>2-4% very fine to fine pyrite. Disseminated, in small veinlets and</p>	117.00	118.00	P009238	1.00	1.235		1.235
			118.00	119.00	P009239	1.00	0.394		0.394

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		in clusters.	119.00	120.00	P009240	1.00	5.810	6.13	6.130
119.70	120.90	Chl	120.00	121.00	P009241	1.00	0.539		0.539
		<b>Chloritisation</b>	121.00	122.00	P009243	1.00	0.022		0.022
		Moderate pervasive chloritisation.	122.00	123.00	P009244	1.00	0.007		0.007
			123.00	124.50	D953066	1.50	<0.005		0.001
			124.50	126.00	D953067	1.50	0.005		0.005
			126.00	127.50	D953068	1.50	0.018		0.018
			127.50	129.00	D953069	1.50	0.011		0.011
			129.00	130.50	D953071	1.50	0.006		0.006
			130.50	132.00	D953072	1.50	0.006		0.006
			132.00	133.50	D953073	1.50	<0.005		0.001
			133.50	135.00	D953074	1.50	<0.005		0.001
			135.00	136.50	D953075	1.50	<0.005		0.001
			136.50	138.00	D953076	1.50	0.005		0.005
			138.00	139.50	D953077	1.50	<0.005		0.001
			139.50	141.00	D953078	1.50	0.010		0.010
140.50	140.80	GP	141.00	142.00	P009245	1.00	0.014		0.014
		<b>Graphite</b>							
		Graphitic argillite. Black foliated aphanitic matrix. Non magnetic.							
		Light carbonatisation.							
		1-2% very fine to fine pyrite (disseminated and in clusters).							
		Sharp contacts.							
141.20	141.50	GP							
		<b>Graphite</b>							
		Graphitic argillite. Same as 140.5-140.8m.							
142.00	142.50	GP	142.00	143.00	P009246	1.00	0.030		0.030
		<b>Graphite</b>							
		Graphitic argillite. Same as 140.5-140.8m.							
143.00	143.30	GP	143.00	144.00	P009247	1.00	0.017		0.017
		<b>Graphite</b>							
		Graphitic argillite. Same as 140.4-140.8m.							
143.50	143.70	GP	144.00	145.00	P009248	1.00	0.005		0.005
		<b>Graphite</b>	145.00	146.00	D953079	1.00	0.005		0.005
		Graphitic argillite. Same as 140.5-140.8m.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			146.00	147.00	D953081	1.00	0.005		0.005
			147.00	148.50	D953082	1.50	0.032		0.032
			148.50	150.00	D953083	1.50	0.015		0.015
			150.00	151.50	D953084	1.50	0.038		0.038
			151.50	153.00	D953086	1.50	0.452		0.452
152.60	152.80	BRE <b>Breccia 45°</b> Breccia or fault with a graphitic matrix very altered. Fragments are pale and are 0.4-1cm. Contact @ 45° TCA.							
152.80	154.70	I2D POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Pale green fine grained matrix with 2-3% Fp phenos (0.4-1cm). Massive and non magnetic.  Tr very fine to fine disseminated pyrite.  Sharp contacts 20-30° TCA	153.00	154.50	D953087	1.50	0.012		0.012
			154.50	156.00	D953088	1.50	0.011		0.011
			156.00	157.50	D953089	1.50	<0.005		0.001
			157.50	159.00	D953091	1.50	<0.005		0.001
			159.00	160.50	D953092	1.50	0.019		0.019
			160.50	162.00	D953093	1.50	0.361		0.361
			162.00	163.00	D953094	1.00	0.011		0.011
			163.00	164.00	D953095	1.00	0.008		0.008
			164.00	165.00	P009249	1.00	0.006		0.006
164.20	164.60	VEI;40;QzCl;;Py0.5; <b>Vein 40 Quartz Chlorite Pyrite0.5%</b> 40 cm Qz-Cl vein with traces of pyrite.							
164.60	165.20	Py03 <b>Pyrite 03%</b> 2-4% very fine to fine pyrite (disseminated and in clusters) in a Qz-Cc syenite.	165.00	166.00	P009250	1.00	0.007		0.007
165.80	168.40	BRE <b>Breccia</b> Breccia. Green angular fragments in a black chloritic aphanitic matrix. Fragments are elongated in the sens of the foliation @ 20-30° TCA.	166.00	167.00	D953096	1.00	0.005		0.005
			167.00	168.00	D953097	1.00	<0.005		0.001
			168.00	169.50	D953098	1.50	<0.005		0.001
			169.50	171.00	D953099	1.50	<0.005		0.001
			171.00	172.00	D953101	1.00	<0.005		0.001
			172.00	173.00	D953102	1.00	<0.005		0.001
			173.00	174.00	P009251	1.00	0.008		0.008
173.30	173.50	Py05 <b>Pyrite 05%</b> 4-6% fine pyrite (disseminated and in clusters) in a graphitic and carbonates injection.	174.00	175.50	D953103	1.50	<0.005		0.001
			175.50	177.00	D953104	1.50	<0.005		0.001
			177.00	178.00	D953105	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
179.40	182.70	Py03 <b>Pyrite 03%</b> 2-4% very fine to fine pyrite. In graphitic and carbonates injections @ 20° TCA. The pyrite is disseminated and in clusters in the injections.	178.00	179.00	D953106	1.00	<0.005		0.001
			179.00	180.00	P009252	1.00	<0.005		0.001
			180.00	181.00	P009253	1.00	0.044		0.044
			181.00	182.00	P009254	1.00	0.015		0.015
			182.00	183.00	P009255	1.00	<0.005		0.001
			183.00	184.50	D953107	1.50	<0.005		0.001
			184.50	186.00	D953108	1.50	<0.005		0.001
			186.00	187.50	D953109	1.50	<0.005		0.001
			187.50	189.00	D953111	1.50	<0.005		0.001
			189.00	190.50	D953112	1.50	<0.005		0.001
			190.50	192.00	D953113	1.50	<0.005		0.001
			192.00	193.50	D953114	1.50	0.005		0.005
			193.50	195.00	D953115	1.50	<0.005		0.001
			195.00	196.50	D953116	1.50	<0.005		0.001
			196.50	198.00	D953117	1.50	<0.005		0.001
			198.00	199.50	D953118	1.50	<0.005		0.001
			199.50	201.00	D953119	1.50	<0.005		0.001
			201.00	202.50	D953121	1.50	<0.005		0.001
			202.50	204.00	D953122	1.50	<0.005		0.001
			204.00	205.50	D953123	1.50	<0.005		0.001
205.50	207.00	D953124	1.50	<0.005		0.001			
207.00	208.50	D953125	1.50	<0.005		0.001			
208.50	210.00	D953126	1.50	<0.005		0.001			
210.00	210.40	BRE <b>Breccia</b> Breccia. Same as 165.8-168.4m.	210.00	211.50	D953127	1.50	<0.005		0.001
			211.50	213.00	D953128	1.50	<0.005		0.001
			213.00	214.50	D953129	1.50	0.005		0.005
			214.50	216.00	D953131	1.50	<0.005		0.001
			216.00	217.50	D953132	1.50	<0.005		0.001
			217.50	219.00	D953133	1.50	<0.005		0.001
			219.00	220.50	D953134	1.50	<0.005		0.001
			220.50	222.00	D953135	1.50	<0.005		0.001
			222.00	223.50	D953136	1.50	<0.005		0.001
			223.50	225.00	D953137	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
229.00	230.50	BRE <b>Breccia</b> Breccia. Same as 165.8-168.4m.	225.00	226.50	D953138	1.50	<0.005		0.001
			226.50	228.00	D953139	1.50	<0.005		0.001
			228.00	229.50	D953141	1.50	<0.005		0.001
			229.50	231.00	D953142	1.50	<0.005		0.001
			231.00	232.50	D953143	1.50	<0.005		0.001
			232.50	234.00	D953144	1.50	<0.005		0.001
			234.00	235.50	D953146	1.50	<0.005		0.001
			235.50	237.00	D953147	1.50	<0.005		0.001
			237.00	238.50	D953148	1.50	<0.005		0.001
			238.50	240.00	D953149	1.50	0.006		0.006
240.00	Fin du sondage Nombre d'échantillons : 193 Nombre d'échantillons QAQC : 16 Longueur totale échantillonnée : 224.30								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
20.00	20.00	P009140	O54Pa	0.00	3.080	2.930
41.00	41.00	P009162	O53Pb	0.00	0.663	0.663
78.00	78.00	P009201	O52Pb	0.00	0.320	0.320
100.00	100.00	P009224	O54Pa	0.00	2.920	2.920
120.00	120.00	P009242	O53Pb	0.00	0.638	0.638
127.50	127.50	D953070	O54Pa	0.00	3.020	3.020
145.00	146.00	D953080	D953079	1.00	<0.005	0.001
150.00	150.00	D953085	m	0.00	<0.005	0.001
156.00	156.00	D953090	O52Pb	0.00	0.318	0.318
169.50	171.00	D953100	D953099	1.50	0.005	0.005
186.00	186.00	D953110	O53Pb	0.00	0.639	0.639
199.50	201.00	D953120	D953119	1.50	<0.005	0.001
213.00	213.00	D953130	O54Pa	0.00	3.060	3.060
226.50	228.00	D953140	D953139	1.50	<0.005	0.001
232.50	232.50	D953145	m	0.00	<0.005	0.001
238.50	238.50	D953150	O52Pb	0.00	0.310	0.310



## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-60	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multidrill	Lot :	
Décrit par : Geneviève Carignan	Du : 2009-05-25	Date de description : 2009-06-04
	Au : 2009-05-29	

Collet

Azimut : 162.14°  
 Plongée : -67.60°  
 Longueur : 247.00 m

UTM

Est	629 974.8
Nord	5 374 321.8
Élévation	282.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	159.75°	-66.40°	Non
Reflex	60.00	161.45°	-65.20°	Non
Reflex	90.00	166.55°	-64.30°	Non
Reflex	120.00	169.25°	-63.30°	Non
Reflex	150.00	168.95°	-62.20°	Non
Reflex	180.00	171.05°	-60.70°	Non
Reflex	240.00	170.25°	-58.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

NAD 83, UTM Zone 17  
 \*\*Indicates changes made  
 Resampled 14-15/09/2010 by K.Wallace.

Dimension de la carotte : NQ Cimenté : Non Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	11.20	MT <b>Casing</b> Casing.							
11.20	104.80	SY POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Grey-greenish aphanitic matrix with 5-7% Fp phenos (0.3-0.5cm). Massive and magnetic. Loc brecciated.  Light carbonatisation with 1-2% Cc injections. Light pervasive chloritisation (dark stringers from 55.6m to xxxm) with local light silicification. Weathering in the fractures until 40m.  1% very fine pyrite. Disseminated or fine stringers.  57-xxxm: 1-2% Fp phenos.  **Locally abundant qtz-calcite veining, as well as local strong silicification - giving a grey colour to unit.	12.00	13.00	P008919	1.00	0.186		0.186
			13.00	14.00	P008920	1.00	0.268		0.268
			14.00	15.00	P008921	1.00	0.577		0.577
			15.00	16.00	P008922	1.00	0.459		0.459
			16.00	17.00	P008923	1.00	0.346		0.346
			17.00	18.00	P008924	1.00	0.131		0.131
			18.00	19.00	P008925	1.00	0.009		0.009
			19.00	20.00	P008926	1.00	0.379		0.379
			20.00	21.00	P008927	1.00	0.848		0.848
			21.00	22.00	P008928	1.00	0.718		0.718
			22.00	23.00	P008929	1.00	1.885		1.885
			23.00	24.00	P008931	1.00	0.784		0.784
			24.00	25.00	P008932	1.00	0.160		0.160
			25.00	26.00	P008933	1.00	0.199		0.199
			26.00	27.00	P008934	1.00	0.460		0.460
			27.00	28.00	P008935	1.00	0.696		0.696
			28.00	29.00	P008936	1.00	0.525		0.525
			29.00	30.00	P008937	1.00	0.122		0.122
			30.00	31.00	P008938	1.00	0.083		0.083
			31.00	32.00	P008939	1.00	0.153		0.153
			32.00	33.00	P008940	1.00	1.095		1.095
			33.00	34.00	P008941	1.00	2.160		2.160
33.40	36.20	Sil <b>Silicification</b> Moderate pervasive silicification.							
33.40	36.20	BRE <b>Breccia</b> Siliceous breccia with 2-7%, up to 10% locally** very fine disseminated pyrite.  **Also has moderate to strong shearing from 33.40 to ~37m.	34.00	35.00	P008942	1.00	5.270	5.23	5.230
			35.00	36.00	P008943	1.00	3.260	3.22	3.220
			36.00	37.00	P008944	1.00	0.789		0.789
36.20	36.90	Ser; Car	37.00	38.00	P008945	1.00	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Sericitisation; Carbonatisation</b>	38.00	39.00	P008947	1.00		0.015
		Light sericitisation and carbonatisation making a foliation @ 30-40° TCA.	39.00	40.00	P008948	1.00		0.007
			40.00	41.00	P008949	1.00		0.010
40.50	42.20	CIS						
		<b>Sheared</b>						
		Moderate to strong shearing at 40-50 DTCA, abundant sericite alteration with chlorite. Moderately siliceous with tr-1% fg py.						
40.70	41.40	Ser; Sil	41.00	42.00	P008950	1.00		0.013
		<b>Sericitisation; Silicification</b>						
		Light sericitisation and light to moderate silicification.						
42.00	57.00	Py02	42.00	43.00	P008951	1.00		0.987
		<b>Pyrite 02%</b>	43.00	44.00	P008952	1.00		0.599
		1-2% very fine disseminated pyrite.	44.00	45.00	P008953	1.00		0.350
			45.00	46.00	P008954	1.00		0.284
			46.00	47.00	P008955	1.00		0.459
			47.00	48.00	P008956	1.00		0.584
			48.00	49.00	P008957	1.00		1.100
			49.00	50.00	P008958	1.00		0.503
			50.00	51.00	P008959	1.00		0.434
			51.00	52.00	P008960	1.00	2.93	2.930
			52.00	53.00	P008961	1.00	7.11	7.110
			53.00	54.00	P008962	1.00	3.90	3.900
			54.00	55.00	P008963	1.00		0.625
			55.00	56.00	P008965	1.00		0.057
55.40	104.80	CIS	56.00	57.00	P008966	1.00		0.011
		<b>Sheared</b>	57.00	58.00	P008967	1.00		<0.005
		Intermittent moderate to strong shearing with sericite/chlorite alteration. Foliation when present is @ 40 to 60 DTCA.	58.00	59.00	P008968	1.00		<0.005
			59.00	60.00	P008969	1.00		<0.005
		** From original log 81-85.30 Breccia. Siliceous matrix brecciated with carbonates injections.	60.00	61.00	P008970	1.00		<0.005
			61.00	62.00	P008971	1.00		<0.005
			62.00	63.00	P008972	1.00		0.008
			63.00	64.00	P008973	1.00		<0.005
			64.00	65.00	P008974	1.00		0.025
			65.00	66.00	P008975	1.00		<0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			66.00	67.00	P008976	1.00		0.006	0.006
			67.00	68.00	P008977	1.00		0.007	0.007
			68.00	69.00	P008978	1.00		0.007	0.007
68.70	78.00	Sil <b>Silicification</b> Light pervasive silicification.	69.00	70.00	P008979	1.00		<0.005	0.001
			70.00	71.00	P008980	1.00		<0.005	0.001
			71.00	72.00	P008981	1.00		<0.005	0.001
71.10	81.00	Py01 <b>Pyrite 01%</b> 1% very fine disseminated pyrite.	72.00	73.00	P008982	1.00		0.014	0.014
			73.00	74.00	P008983	1.00		0.005	0.005
			74.00	75.00	P008984	1.00		0.014	0.014
			75.00	76.00	P008985	1.00		0.077	0.077
			76.00	77.00	P008987	1.00		0.048	0.048
			77.00	78.00	P008988	1.00		0.385	0.385
78.00	81.00	Ser <b>Sericitisation</b> Moderate sericitisation with 2-3% white Qz veins (irregulars but mostly ~90° TCA, from 0.5 to 13cm). Making a foliation @ 30-50° TCA.	78.00	79.00	P008989	1.00		0.280	0.280
78.60	79.00	VEI;0;Qz Ce;;; <b>Vein 0 Quartz Calcite</b> qtz-calcite vein up to 6cm thick. "worm-like" in appearance	79.00	80.00	P008990	1.00		0.638	0.638
			80.00	81.00	P008991	1.00		0.182	0.182
81.00	85.30	Sil; Car <b>Silicification; Carbonatisation</b> Moderate pervasive silicification and carbonatisation in injections.  84.3-84.8m: Moderate sericitisation and silicification making a foliation @ ~90° TCA.							
81.00	104.80	Py02 <b>Pyrite 02%</b> 2-3% very fine disseminated pyrite.	81.00	82.00	P008992	1.00		1.695	1.695
			82.00	83.00	P008993	1.00	3.60	3.090	3.600
			83.00	84.00	P008994	1.00		2.460	2.460
			84.00	85.00	P008995	1.00		2.470	2.470
			85.00	86.00	P008996	1.00		3.780	3.780
85.30	87.85	I2D POR <b>Syenite Porphyry Intrusive</b> Intrusive rock. Grey-greenish aphanitic matrix with 3-5% Fp phenos (0.5-1cm).	86.00	87.00	P008997	1.00		0.927	0.927
			87.00	88.00	P008998	1.00		1.360	1.360

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		Foliated @ 50-60° TCA and non magnetic.  Moderate sericitisation and light silicification.  1-2% very fine disseminated pyrite.  Contacts sharp @ 50-60° TCA.						
87.85	99.90	SiI	88.00	89.00	P008999	1.00	0.017	0.017
		<b>Silicification</b>	89.00	90.00	P009000	1.00	0.053	0.053
		Light silicification and albitisation as injections making light brecciation.	90.00	91.00	P009001	1.00	0.380	0.380
			91.00	92.00	P009002	1.00	0.106	0.106
			92.00	93.00	P009004	1.00	0.010	0.010
			93.00	94.00	P009005	1.00	0.069	0.069
			94.00	95.00	P009006	1.00	0.228	0.228
			95.00	96.00	P009007	1.00	0.008	0.008
			96.00	97.00	P009008	1.00	0.013	0.013
			97.00	98.00	P009009	1.00	0.150	0.150
			98.00	99.00	P009010	1.00	0.991	0.991
			99.00	100.00	P009011	1.00	1.020	1.020
99.90	100.90	Chi	100.00	101.00	P009012	1.00	0.183	0.183
		<b>Chloritisation</b>	101.00	102.00	P009013	1.00	0.178	0.178
		Light to moderate chloritisation.	102.00	103.00	P009014	1.00	0.238	0.238
			103.00	104.00	P009015	1.00	0.011	0.011
			104.00	105.00	P009016	1.00	0.034	0.034
104.80	130.65	BA	105.00	106.50	D911284	1.50	0.007	0.007
		<b>Mafic Meta-Volcanic</b>	106.50	108.00	D911286	1.50	0.011	0.011
		Pale green to Dark green to loc almost black aphanitic to fine grained matrix. Foliation @ 50-60° TCA. Fractured and non magnetic. Loc 2-3% small brown mineral (leucoxenes?).  1% Cc veins and injections.  Moderate to loc high chloritisation and loc seericitisation along foliation. Loc bleaching.  Tr-1% fine (loc cubic) disseminated pyrite and in fine stringers. Upper contact @ 70° TCA.	108.00	109.50	D911287	1.50	0.075	0.075

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
109.20	112.00	SCH; FRC; FAI <b>Schistosed ; Fractured; Fault</b> Core is highly schistosed and fractured.  ** also strong faulting with minor gouge in this interval. Very strong silicification from 109.20-110m.	109.50	111.00	D911288	1.50	0.117		0.117
			111.00	112.50	D911289	1.50	0.019		0.019
			112.50	114.00	D911291	1.50	0.082		0.082
			114.00	115.00	P009017	1.00	1.830		1.830
114.20	115.10	Py02 <b>Pyrite 02%</b> 1-3% fine disseminated pyrite (loc cubic) and in fine stringers.	115.00	116.00	P009018	1.00	0.019		0.019
			116.00	117.00	D911292	1.00	0.116		0.116
			117.00	118.50	D911293	1.50	<0.005		0.001
			118.50	120.00	D911294	1.50	<0.005		0.001
			120.00	121.50	D911295	1.50	<0.005		0.001
			121.50	123.00	D911296	1.50	<0.005		0.001
			123.00	124.50	D911297	1.50	<0.005		0.001
			124.50	126.00	D911298	1.50	<0.005		0.001
			126.00	127.50	D911299	1.50	<0.005		0.001
			127.50	129.00	D911301	1.50	<0.005		0.001
			129.00	130.50	D911302	1.50	<0.005		0.001
130.65	166.80	CG; S <b>Conglomerat; Sediment (Meta incl.)</b> **Polymictic conglomerate with elgonate fragments in a chlorite/argillite matrix. Well foliated @ 50-60 DTCA. Overall colour is dark grey-brown. Locally weakly carbonatized. Also some greywacke and argillite interbedded. Rare local coarse py blebs.	130.50	132.00	D911303	1.50	0.122		0.122
132.00	166.80	Ser <b>Sericitisation</b> Light to loc moderate sericitisation along foliation.	132.00	133.50	D911304	1.50	0.355		0.355
			133.50	135.00	D911305	1.50	0.117		0.117
			135.00	136.50	D911306	1.50	0.199		0.199
			136.50	138.00	D911307	1.50	0.327		0.327
138.00	138.80	Py02 <b>Pyrite 02%</b> 1-2% fine disseminated pyrite and in stringers.	138.00	139.00	P009019	1.00	0.502		0.502
			139.00	140.00	D911308	1.00	0.120		0.120
			140.00	141.00	D911309	1.00	0.449		0.449
			141.00	142.50	D911311	1.50	0.320		0.320
			142.50	144.00	D911312	1.50	0.313		0.313
			144.00	145.50	D911313	1.50	0.344		0.344

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
151.40	151.70	Py04 <b>Pyrite 04%</b> Blobs(1-2cm) of pyrite and disseminated loc cubic pyrite.	145.50	147.00	D911314	1.50	0.330		0.330
			147.00	148.50	D911315	1.50	0.431		0.431
			148.50	150.00	D911316	1.50	0.076		0.076
			150.00	151.00	P009020	1.00	0.164		0.164
			151.00	152.00	P009022	1.00	0.103		0.103
			152.00	153.00	P009023	1.00	0.007		0.007
			153.00	154.00	P009024	1.00	0.015		0.015
			154.00	155.00	P009025	1.00	0.014		0.014
			155.00	156.00	P009026	1.00	<0.005		0.001
			156.00	157.50	D911317	1.50	<0.005		0.001
			157.50	159.00	D911318	1.50	<0.005		0.001
			159.00	160.50	D911319	1.50	<0.005		0.001
			160.50	162.00	D911321	1.50	<0.005		0.001
			162.00	163.50	D911322	1.50	0.005		0.005
			163.50	165.00	D911323	1.50	<0.005		0.001
165.00	166.50	D911324	1.50	<0.005		0.001			
166.50	168.00	D911325	1.50	<0.005		0.001			
166.80	247.00	UM; S; BA <b>Ultramafic Volcanic (incl. Flows); Sediment (Meta incl.); Mafic Meta-Volcanic</b> **Well foliated, banded, ultramafics with interbedding of meta sediment and mafic volcanics. Abundant calcite flooding/veining, with abundant talc/serpentine alteration. Foliation is at 50-90 DTCA. Very rare coarse blebs of py. Sedimentary and mafic zones are less altered than ultramafic zones.							
166.80	179.70	Ser; Car; Chl <b>Sericitisation; Carbonatisation; Chloritisation</b> High sericitisation, carbonatisation and light chloritisation making a high foliation @ 50° TCA.							
166.80	247.00	FOL <b>Foliation</b> Highly foliated @ 40-90° TCA.  225-225.5m: Fractured.  **Evidence of faulting between 212-213m - abundant gouge. Faulting between 246 and 247 - moderate gouge.	168.00	169.50	D911326	1.50	<0.005		0.001
			169.50	171.00	D911327	1.50	<0.005		0.001
			171.00	172.50	D911328	1.50	0.055		0.055
			172.50	174.00	D911329	1.50	0.005		0.005
			174.00	175.50	D911331	1.50	<0.005		0.001
175.50	177.00	D911332	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
187.15	218.60	Car; Chl; TC <b>Carbonatisation; Chloritisation; Talc</b> High carbonatisation and chloritisation and loc talc?.	177.00	178.50	D911333	1.50	0.011		0.011
			178.50	180.00	D911334	1.50	0.005		0.005
			180.00	181.50	D911335	1.50	<0.005		0.001
			181.50	183.00	D911336	1.50	<0.005		0.001
			183.00	184.50	D911337	1.50	<0.005		0.001
			184.50	186.00	D911338	1.50	<0.005		0.001
			186.00	187.50	D911339	1.50	<0.005		0.001
			187.50	189.00	D911341	1.50	<0.005		0.001
			189.00	190.50	D911342	1.50	<0.005		0.001
			190.50	192.00	D911343	1.50	<0.005		0.001
			192.00	193.50	D911344	1.50	<0.005		0.001
			193.50	195.00	D911346	1.50	<0.005		0.001
			195.00	196.50	D911347	1.50	<0.005		0.001
			196.50	198.00	D911348	1.50	<0.005		0.001
			198.00	199.50	D911349	1.50	<0.005		0.001
			199.50	201.00	D911351	1.50	<0.005		0.001
			201.00	202.50	D911352	1.50	0.005		0.005
			202.50	204.00	D911353	1.50	<0.005		0.001
			204.00	205.50	D911354	1.50	0.040		0.040
			205.50	207.00	D911355	1.50	<0.005		0.001
			207.00	208.50	D911356	1.50	<0.005		0.001
			208.50	210.00	D911357	1.50	<0.005		0.001
			210.00	211.50	D911358	1.50	<0.005		0.001
			211.50	213.00	D911359	1.50	<0.005		0.001
			213.00	214.50	D911361	1.50	<0.005		0.001
			214.50	216.00	D911362	1.50	0.005		0.005
			216.00	217.50	D911363	1.50	<0.005		0.001
			217.50	219.00	D911364	1.50	<0.005		0.001
219.00	220.50	D911365	1.50	<0.005		0.001			
220.50	222.00	D911366	1.50	<0.005		0.001			
222.00	223.50	D911367	1.50	0.019		0.019			
223.50	225.00	D911368	1.50	0.024		0.024			
225.00	226.50	D911369	1.50	0.018		0.018			



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
228.10	247.00	Car; Chl <b>Carbonatisation; Chloritisation</b> Same as 187.15-218.6m.	226.50	228.00	D911371	1.50	0.037		0.037	
			228.00	229.50	D911372	1.50	0.019		0.019	
			229.50	231.00	D911373	1.50	0.087		0.087	
			231.00	232.50	D911374	1.50	<0.005		0.001	
			232.50	234.00	D911375	1.50	<0.005		0.001	
			234.00	235.50	D911376	1.50	0.036		0.036	
			235.50	237.00	D911377	1.50	<0.005		0.001	
			237.00	238.50	D911378	1.50	0.005		0.005	
			238.50	240.00	D911379	1.50	<0.005		0.001	
			240.00	241.50	D911381	1.50	<0.005		0.001	
			241.50	243.00	D911382	1.50	<0.005		0.001	
			243.00	244.50	D911383	1.50	<0.005		0.001	
			244.50	246.00	D911384	1.50	<0.005		0.001	
			246.00	247.00	D911386	1.00	<0.005		0.001	
			247.00	Fin du sondage Nombre d'échantillons : 192 Nombre d'échantillons QAQC : 19 Longueur totale échantillonnée : 235.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
22.00	22.00	P008930	O54Pa	0.00	2.970	2.970
37.00	37.00	P008946	O53Pb	0.00	0.625	0.625
54.00	54.00	P008964	O52Pb	0.00	0.311	0.311
75.00	75.00	P008986	O54Pa	0.00	2.960	2.960
91.00	91.00	P009003	O53Pb	0.00	0.619	0.619
105.00	105.00	D911285	m	0.00	<0.005	0.001
111.00	111.00	D911290	O52Pb	0.00	0.317	0.317
126.00	127.50	D911300	D911299	1.50	<0.005	0.001
140.00	140.00	D911310	O53Pb	0.00	0.710	0.710
150.00	150.00	P009021	O52Pb	0.00	0.311	0.311
159.00	160.50	D911320	D911319	1.50	0.006	0.006
172.50	172.50	D911330	O54Pa	0.00	3.160	3.160
186.00	187.50	D911340	D911339	1.50	<0.005	0.001
192.00	192.00	D911345	m	0.00	<0.005	0.001
198.00	198.00	D911350	O52Pb	0.00	0.332	0.332
211.50	213.00	D911360	D911359	1.50	<0.005	0.001
225.00	225.00	D911370	O53Pb	0.00	0.641	0.641
238.50	240.00	D911380	D911379	1.50	<0.005	0.001
244.50	244.50	D911385	m	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-61	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multi Drill	Lot :	
Décrit par : Aidamir Chreoukh	Du : 2009-05-31	Date de description : 2009-06-03
	Au : 2009-06-03	

Collet

Azimut : 339.75°  
 Plongée : -65.60°  
 Longueur : 123.00 m

UTM

Est	629 926.8
Nord	5 374 341.8
Élévation	281.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	338.75°	-63.10°	Non
Reflex	60.00	343.35°	-62.60°	Non
Reflex	90.00	344.75°	-61.50°	Non
Reflex	120.00	341.05°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

UTM NAD 83 Zone 17.

Hole surveyed in Nov 2009 by Descarreaux.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	24.00	MT <b>Casing</b> overburden						
24.00	44.90	SY POR; AMY <b>Syenite Porphyry Intrusive; Amygdalaire</b> dark grey to greenish grey to purple to wine red, fine-med. matrix, 10-15% mm-cm sized trace amygdule mainly chloritized, loc. tecto-brecciated with chloritic matrix, 5-10% 5cm, mod-highly chloritized, loc. weak-mod. K-altered, overall Tr-1% diss. Py with local concentrations 1-3% finely diss. Py to coarse to cubic loc., Tr. of Cp loc, 1-5% diss. magnetite, undfined highly fractured, faulted? lower CT	24.00	25.50	D953151	1.50	0.058	0.058
			25.50	27.00	D953152	1.50	0.127	0.127
			27.00	28.50	D953153	1.50	0.034	0.034
			28.50	30.00	D953154	1.50	0.009	0.009
			30.00	31.00	P009523	1.00	0.083	0.083
			31.00	32.00	P009524	1.00	0.358	0.358
			32.00	33.00	P009525	1.00	<0.005	0.001
			33.00	34.00	P009526	1.00	0.194	0.194
			34.00	35.00	P009527	1.00	0.016	0.016
			35.00	36.00	P009528	1.00	0.105	0.105
			36.00	37.00	P009529	1.00	0.051	0.051
			37.00	38.00	P009530	1.00	0.014	0.014
			38.00	39.00	P009531	1.00	0.089	0.089
			39.00	40.00	P009533	1.00	0.006	0.006
			40.00	41.00	P009534	1.00	0.019	0.019
			41.00	42.00	P009535	1.00	0.006	0.006
			42.00	43.00	P009536	1.00	0.019	0.019
			43.00	44.00	P009537	1.00	0.125	0.125
			44.00	45.00	M79686	1.00	0.038	0.038
44.90	123.00	AN; FOL <b>Intermediate Volcanic (Flow); Foliation</b> dark green to greenish beige, fine-med. grained, weak-mod. foliated@0-40°TCA, loc. tect-to hydro-brecciated with silica-Carb. matrix, +/+ sericitized&epidotized, 1-3% broken core, 5-15% /p>	45.00	46.00	M79687	1.00	0.006	0.006
			46.00	47.00	M79688	1.00	<0.005	0.001
			47.00	48.00	M79689	1.00	<0.005	0.001
44.90	45.50	FRC <b>Fractured</b> 70-85% highly fractured, strongly altered fragments with 10cm Qtz-Carb injections with sericite stringers@60°TCA, Qtz-Carb injection cut by fault plan?@10°TCA						
47.70	48.00	FRC <b>Fractured</b> broken core	48.00	49.00	M79690	1.00	<0.005	0.001
			49.00	50.00	M79691	1.00	<0.005	0.001
			50.00	51.00	M79692	1.00	0.008	0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			51.00	52.00	M79693	1.00	<0.005		0.001
			52.00	53.00	M79694	1.00	<0.005		0.001
			53.00	54.00	M79695	1.00	<0.005		0.001
53.60	53.95	S10	54.00	54.90	M79696	0.90	<0.005		0.001
		<b>Chert 25°</b>	54.90	55.90	M79697	1.00	<0.005		0.001
		light green to greenish beige, cherty unit could be silicified or	55.90	56.40	M79698	0.50	<0.005		0.001
		bleached? Iloc. microfractured with silica-Carb fillings, 1-3%	56.40	57.50	M79699	1.10	<0.005		0.001
		diss. to coarse Py							
56.50	57.15	S10	57.50	58.50	M79701	1.00	<0.005		0.001
		<b>Chert 25°</b>	58.50	59.50	M79702	1.00	<0.005		0.001
		light green to greenish beige, cherty unit could be silicified or	59.50	60.50	M79704	1.00	<0.005		0.001
		bleached? Iloc. microfractured with silica-Carb fillings, 1-3%	60.50	61.50	M79705	1.00	<0.005		0.001
		diss. to coarse Py	61.50	62.50	M79706	1.00	<0.005		0.001
			62.50	63.50	M79707	1.00	<0.005		0.001
			63.50	64.50	M79708	1.00	<0.005		0.001
			64.50	65.50	M79709	1.00	<0.005		0.001
			65.50	66.50	M79710	1.00	<0.005		0.001
			66.50	67.50	M79711	1.00	<0.005		0.001
			67.50	68.50	M79712	1.00	<0.005		0.001
			68.50	69.50	M79713	1.00	<0.005		0.001
			69.50	70.50	M79714	1.00	<0.005		0.001
			70.50	71.50	M79715	1.00	<0.005		0.001
			71.50	72.50	M79716	1.00	<0.005		0.001
			72.50	73.50	M79717	1.00	<0.005		0.001
			73.50	74.50	M79718	1.00	<0.005		0.001
			74.50	75.50	M79719	1.00	<0.005		0.001
			75.50	76.50	D953155	1.00	<0.005		0.001
			76.50	78.00	D953156	1.50	<0.005		0.001
			78.00	79.50	D953157	1.50	<0.005		0.001
78.70	80.10	CD40	79.50	81.00	D953158	1.50	<0.005		0.001
		<b>Calcedony 40</b>	81.00	82.50	D953159	1.50	<0.005		0.001
		light green to greenish beige, 1-3% Py in form of stringers							
		associated to replacive chert bands or VI and Qtz-Carb							
		injections							
82.35	82.90	CD40	82.50	84.00	D953161	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
85.80	86.50	<b>Calcedony 40</b>	84.00	85.30	D953162	1.30	<0.005		0.001
		light green to greenish beige, 1-3% Py in form of stringers associated to replacive chert bands or VI and Qtz-Carb injections	85.30	85.80	M79721	0.50	<0.005		0.001
		<b>Py05</b>	85.80	86.50	M79722	0.70	<0.005		0.001
		<b>Pyrite 05%</b>	86.50	87.00	M79723	0.50	<0.005		0.001
		1-5% diss. to patches of Py associated to cherty bands along CA	87.00	88.50	D953163	1.50	<0.005		0.001
			88.50	90.00	D953164	1.50	<0.005		0.001
			90.00	91.50	D953165	1.50	<0.005		0.001
			91.50	93.00	D953166	1.50	<0.005		0.001
			93.00	94.50	D953167	1.50	0.007		0.007
			94.50	96.00	D953168	1.50	<0.005		0.001
			96.00	97.50	D953169	1.50	<0.005		0.001
			97.50	99.00	D953171	1.50	<0.005		0.001
			99.00	100.50	D953172	1.50	<0.005		0.001
			100.50	102.00	D953173	1.50	<0.005		0.001
			102.00	103.50	D953174	1.50	<0.005		0.001
			103.50	105.00	D953175	1.50	<0.005		0.001
			105.00	105.90	D953176	0.90	<0.005		0.001
			105.90	106.90	M79724	1.00	<0.005		0.001
106.10	106.85	Epi; Ser	106.90	107.90	M79725	1.00	0.005		0.005
		<b>Epidotisation; Sericitisation</b>	107.90	108.40	M79726	0.50	<0.005		0.001
		strongly foliated@0-25°TCA, mod. sericitized, epidotized stringers along foliation, smokey to white Qtz-Carb injections@40°TCA,							
108.40	108.90	FRC	108.40	108.90	M79727	0.50	<0.005		0.001
		<b>Fractured</b>	108.90	109.40	M79728	0.50	<0.005		0.001
		strongly fractured to sub-brecciated, /p>	109.40	111.00	D953177	1.60	<0.005		0.001
111.00	123.00	SW	111.00	112.50	D953178	1.50	<0.005		0.001
		<b>Stockwork</b>	112.50	114.00	D953179	1.50	0.005		0.005
		10-15% smokey to white Qtz-Carb injections, /p>	114.00	115.00	D953181	1.00	<0.005		0.001
			115.00	116.00	D953182	1.00	<0.005		0.001
			116.00	117.00	M79729	1.00	<0.005		0.001
			117.00	118.00	M79730	1.00	<0.005		0.001
	118.00	119.00	M79731	1.00	<0.005		0.001		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
122.60	123.00	BX <b>Breccia</b> tecto-brecciated with silica-carb loc. epidotized	119.00	120.00	M79732	1.00	<0.005		0.001
			120.00	121.00	M79733	1.00	<0.005		0.001
			121.00	122.00	M79734	1.00	<0.005		0.001
			122.00	123.00	M79735	1.00	<0.005		0.001
123.00	Fin du sondage Nombre d'échantillons : 90 Nombre d'échantillons QAQC : 7 Longueur totale échantillonnée : 99.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
38.00	39.00	P009532	O53Pb	1.00	0.647	0.647
56.40	57.50	M79700	O6Pc	1.10	1.560	1.560
58.50	59.50	M79703	O6Pc	1.00	<0.005	0.001
74.50	75.50	M79720	O6Pc	1.00	1.055	1.055
81.00	82.50	D953160	D953159	1.50	<0.005	0.001
96.00	96.00	D953170	O53Pb	0.00	0.663	0.663
112.50	114.00	D953180	D953179	1.50	<0.005	0.001



## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-62	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multidrill	Lot :	
Décrit par : Geneviève Carignan	Du : 2009-06-02	Date de description : 2009-06-09
	Au : 2009-06-06	

Collet

Azimut : 191.09°  
 Plongée : -56.10°  
 Longueur : 300.00 m

UTM

Est	630 819.3
Nord	5 374 103.2
Élévation	297.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	190.05°	-56.30°	Non
Reflex	60.00	192.45°	-54.70°	Non
Reflex	96.00	191.75°	-52.70°	Non
Reflex	120.00	190.25°	-51.70°	Non
Reflex	210.00	189.65°	-45.40°	Non
Reflex	240.00	187.75°	-43.80°	Non
Reflex	270.00	189.75°	-42.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

Resampled by Moustapha Seck 14/09/2010  
 \*Core not recovered from 88 to 89.2 m.

NAD 83, UTM Zone 17

Hole surveyed in November 2009 by Descarreaux.

Dimension de la carotte : NQ	Cimenté : Non	Entreposé : Oui
------------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	15.30	MT <b>Casing</b> Casing.						
15.30	68.50	S; RUB <b>Sediment (Meta incl.); Banded</b> Dark to pale green fine grained banded matrix. Highly foliated @ 40° TCA and non magnetic. 1-2% injections of silice with pyrite and rounded red-orange chert (jasp?) fragments(2cm-5cm) or as bands in the sens of the foliation (from 29.3m to 68.5).  Tr CCc veins @ 20° TCA.  Light to loc moderatly chloritized, light carbonatisation and loc light sericitisation.  Tr very fine to fine (loc cubic) pyrite. Disseminated and in veinlets (0.2cm) @ 30-40° TCA.	15.30	16.50	D953183	1.20	<0.005	0.001
			16.50	18.00	D953184	1.50	0.007	0.007
			18.00	19.50	D953186	1.50	0.050	0.050
			19.50	21.00	D953187	1.50	0.013	0.013
			21.00	22.50	D953188	1.50	0.008	0.008
			22.50	24.00	D953189	1.50	0.043	0.043
			24.00	25.50	D953191	1.50	0.031	0.031
			25.50	27.00	D953192	1.50	0.010	0.010
			27.00	28.00	D953193	1.00	0.015	0.015
			28.00	29.00	P003725	1.00	0.018	0.018
			29.00	30.00	P003727	1.00	0.022	0.022
			30.00	31.50	D953194	1.50	0.006	0.006
			31.50	33.00	D953195	1.50	0.007	0.007
			33.00	34.50	D953196	1.50	<0.005	0.001
			34.50	36.00	D953197	1.50	<0.005	0.001
			36.00	37.50	D953198	1.50	<0.005	0.001
			37.50	39.00	D953199	1.50	<0.005	0.001
			39.00	40.50	D953201	1.50	0.005	0.005
			40.50	42.00	D953202	1.50	0.085	0.085
			42.00	43.50	D953203	1.50	0.015	0.015
			43.50	45.00	D953204	1.50	0.043	0.043
			45.00	46.50	D953205	1.50	0.025	0.025
			46.50	48.00	D953206	1.50	0.087	0.087
			48.00	49.00	D953207	1.00	0.015	0.015
			49.00	50.00	P003728	1.00	0.024	0.024
			50.00	51.00	P003729	1.00	0.014	0.014
50.15	50.25	VEI;10;Qz;;55°;Py01; <b>Vein 10 Quartz 55° Pyrite01%</b> 10 cm smokey Qz vein with 1-2% very fine pyrite.	51.00	52.50	D953208	1.50	0.013	0.013
			52.50	54.00	D953209	1.50	0.046	0.046
			54.00	55.50	D953211	1.50	0.024	0.024
55.50	68.50	Blch <b>Bleaching</b>	55.50	57.00	D953212	1.50	0.022	0.022
			57.00	58.50	D953213	1.50	0.027	0.027

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
Cm to dm zones of bleaching in the sens of the foliation.			58.50	60.00	D953214	1.50	0.023		0.023			
			60.00	61.50	D953215	1.50	0.023		0.023			
			61.50	63.00	D953216	1.50	0.048		0.048			
			63.00	64.50	D953217	1.50	0.044		0.044			
			64.50	66.00	D953218	1.50	0.094		0.094			
			66.00	67.50	D953219	1.50	0.048		0.048			
			67.50	69.00	D953221	1.50	0.080		0.080			
			69.00	70.50	D953222	1.50	0.007		0.007			
			70.50	72.00	D953223	1.50	0.009		0.009			
			72.00	73.50	D953224	1.50	0.005		0.005			
68.50 92.50 BA <b>Mafic Meta-Volcanic</b> Pale green to loc dark green fine grained matrix. Massive with foliated zones @ 50° TCA. Non magnetic.			73.50	75.00	D953225	1.50	0.006		0.006			
			Tr white Qz injections.			75.00	76.50	D953226	1.50	0.009		0.009
						76.50	78.00	D953227	1.50	0.006		0.006
			Light sericitisation along foliation and loc light chloritisation.			78.00	79.50	D953228	1.50	0.022		0.022
						79.50	81.00	D953229	1.50	0.006		0.006
			Tr fine disseminated pyrite.									
Upper contact @ 455° TCA.												
80.90 86.80 Ser <b>Sericitisation</b> Moderate sericitisation alog foliation.			81.00	82.50	D953231	1.50	<0.005		0.001			
			82.50	84.00	D953232	1.50	0.005		0.005			
			80.90 86.80 FOL <b>Foliation</b> Light to moderate foliation @ 40-50° TCA.			84.00	85.50	D953233	1.50	0.005		0.005
						85.50	87.00	D953234	1.50	<0.005		0.001
						87.00	88.00	D953235	1.00	0.007		0.007
88.00 89.20 CNR <b>Core Not recovered</b> Grinded.			89.20	91.00	D953236	1.80	0.007		0.007			
89.50 90.20 FRC <b>Fractured</b> Broken core.												
			91.00	92.50	D953237	1.50	0.099		0.099			
92.50 107.30 S; RUB <b>Sediment (Meta incl.); Banded</b> Same as 15.3-68.5m.			92.50	93.50	D953238	1.00	0.210		0.210			
			93.50	95.00	D953239	1.50	0.088		0.088			
			95.00	96.00	D953241	1.00	0.038		0.038			
			96.00	97.00	D953242	1.00	0.034		0.034			
Highly foliated @ 30-40° TCA and non magnetic. 1% red-orange												

Corporation Minière Osisko Div. Exploration

Description		Analyse							
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
107.30	119.50	rounded chert (jasp?) fragments (2-4cm, loc with tr of pyrite in it) (loc bands) in the sens of the foliation.	97.00	98.00	P003730	1.00	0.042		0.042
			98.00	99.00	P003731	1.00	0.090		0.090
		Tr white Qz injections.	99.00	100.50	D953243	1.50	0.026		0.026
			100.50	102.00	D953244	1.50	0.057		0.057
		Light to moderate chloritisation, light sericitisation and bleached zones.	102.00	103.50	D953246	1.50	0.030		0.030
			103.50	105.00	D953247	1.50	0.027		0.027
		Upper contact @ 50° TCA.	105.00	106.50	D953248	1.50	0.102		0.102
			106.50	108.00	D953249	1.50	0.005		0.005
		Tr very fine disseminated pyrite and in the fragments.							
		BA	108.00	109.50	D953251	1.50	0.008		0.008
		<b>Mafic Meta-Volcanic</b>	109.50	111.00	D953252	1.50	0.057		0.057
		Pale green fine grained matrix. Non magentic. Light foliation @ 40-50° TCA. Homogenous.	111.00	112.50	D953253	1.50	0.005		0.005
			112.50	114.00	D953254	1.50	0.016		0.016
		2-3% Qz veins (1-5cm) @ 60-70° TCA and injections.	114.00	115.50	D953255	1.50	0.010		0.010
	115.50	117.00	D953256	1.50	0.009		0.009		
Light sericitisation along foliation and associated with white Qz injections and loc light chloritisation and bleached zones in the first meter.	117.00	118.50	D953257	1.50	0.008		0.008		
	118.50	119.50	D953258	1.00	0.014		0.014		
Tr-1% very fine to fine disseminated pyrite.									
Upper contact @ 50° TCA (maybe gradual).									
119.50	300.00	S; T1A	119.50	121.00	D953259	1.50	0.058		0.058
		<b>Sediment (Meta incl.); Fault Breccia</b>	121.00	122.00	D953261	1.00	0.099		0.099
		Dark to pale green to beige fine grained to aphanitic banded matrix.	122.00	123.00	D953262	1.00	0.015		0.015
		High foliation @ 50° TCA and loc folded. Tr rounded fragments of grey chert (3-5cm) and white Qz rounded fragments in the sens of the foliation.	123.00	124.00	P003732	1.00	0.038		0.038
			124.00	125.00	P003733	1.00	0.028		0.028
		Loc horizons of small round grey Qz (greywacke ?).	125.00	126.00	P003734	1.00	0.023		0.023
		Locally brecciated.	126.00	127.50	D953263	1.50	0.168		0.168
			127.50	129.00	D953264	1.50	0.029		0.029
		1% white Qz injections.	129.00	130.50	D953265	1.50	0.026		0.026
			130.50	132.00	D953266	1.50	0.019		0.019
		Moderate sericitisation and chloritisation along foliation and light fuchsitization and silicification.	132.00	133.50	D953267	1.50	0.007		0.007
			133.50	135.00	D953268	1.50	0.010		0.010
		Upper contact @ 50° TCA.							
		137.4-145.5: Light foliation @ 40° TCA.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
133.70	134.60	Blch <b>Bleaching</b> Moderate to high bleaching with sharp contacts @ 30° TCA.	135.00	136.50	D953269	1.50	0.010		0.010
			136.50	138.00	D953271	1.50	0.015		0.015
			138.00	139.50	D953272	1.50	0.006		0.006
			139.50	141.00	D953273	1.50	0.006		0.006
			141.00	142.50	D953274	1.50	0.005		0.005
			142.50	144.00	D953275	1.50	<0.005		0.001
			144.00	145.50	D953276	1.50	<0.005		0.001
			145.50	147.00	D953277	1.50	<0.005		0.001
			147.00	148.00	D953278	1.00	0.007		0.007
			148.00	149.00	D953279	1.00	0.006		0.006
			149.00	150.00	P003749	1.00	0.008		0.008
			150.00	151.00	P003750	1.00	0.080		0.080
			151.00	152.00	D953281	1.00	0.008		0.008
			152.00	153.00	D953282	1.00	0.014		0.014
			153.00	154.50	D953283	1.50	<0.005		0.001
153.70	177.00	FCT <b>Fuchsitization</b> Light fuchsitization along foliation.	154.50	156.00	D953284	1.50	<0.005		0.001
			156.00	157.50	D953286	1.50	0.010		0.010
			157.50	159.00	D953287	1.50	0.005		0.005
			159.00	160.50	D953288	1.50	<0.005		0.001
			160.50	162.00	D953289	1.50	<0.005		0.001
161.60	162.00	CNR <b>Core Not recovered</b> 40 cm core not recovered.	162.00	163.00	P003735	1.00	0.032		0.032
			163.00	164.00	P003736	1.00	0.006		0.006
			164.00	165.00	P003737	1.00	0.013		0.013
			165.00	166.50	D953291	1.50	0.024		0.024
			166.50	168.00	D953292	1.50	0.008		0.008
			168.00	169.50	D953293	1.50	<0.005		0.001
			169.50	171.00	D953294	1.50	<0.005		0.001
			171.00	172.00	P003738	1.00	0.090		0.090
171.70	172.00	Py02 <b>Pyrite 02%</b> 1-2% very fine disseminated pyrite in a siliceous-chlorite matrix.	172.00	173.00	P003739	1.00	0.017		0.017
			173.00	174.00	D953295	1.00	<0.005		0.001
			174.00	175.50	D953296	1.50	<0.005		0.001
			175.50	177.00	D953297	1.50	<0.005		0.001
177.00	240.00	FCT; Sil	177.00	178.50	D953298	1.50	0.032		0.032

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
<b>Fuchsitization; Silicification</b>			178.50	180.00	D953299	1.50	<0.005	0.001
Moderate to light fuchsitization along foliation and in the fragments.			180.00	181.50	D953301	1.50	0.006	0.006
			181.50	183.00	D953302	1.50	<0.005	0.001
221.8-225.1m: moderate silicification.			183.00	184.50	D953303	1.50	0.091	0.091
			184.50	186.00	D953304	1.50	0.011	0.011
232.0-236.9m: moderate silicification.			186.00	187.50	D953305	1.50	0.018	0.018
			187.50	189.00	D953306	1.50	0.170	0.170
			189.00	190.50	D953307	1.50	0.032	0.032
			190.50	192.00	D953308	1.50	0.049	0.049
			192.00	193.00	P003740	1.00	0.017	0.017
			193.00	194.00	P003741	1.00	0.049	0.049
			194.00	195.00	P003742	1.00	0.061	0.061
			195.00	196.50	D953309	1.50	0.033	0.033
			196.50	198.00	D953311	1.50	0.216	0.216
			198.00	199.00	D953312	1.00	0.029	0.029
			199.00	200.00	D953313	1.00	0.015	0.015
			200.00	201.60	D953314	1.60	0.012	0.012
			201.60	203.10	P003766	1.50	0.006	0.006
			203.10	204.50	D953315	1.40	<0.005	0.001
			204.50	206.00	D953316	1.50	<0.005	0.001
			206.00	207.00	P003743	1.00	0.049	0.049
206.70	208.10	Py02	207.00	208.00	P003744	1.00	0.082	0.082
<b>Pyrite 02%</b>			208.00	209.00	P003745	1.00	0.005	0.005
2% very fine disseminated pyrite (along the foliation).			209.00	210.00	P003746	1.00	<0.005	0.001
			210.00	211.00	P003747	1.00	0.023	0.023
			211.00	211.60	P003748	0.60	0.082	0.082
			211.60	212.50	P003767	0.90	0.007	0.007
			212.50	213.00	P003751	0.50	0.010	0.010
			213.00	214.00	P003752	1.00	0.020	0.020
			214.00	215.00	P003753	1.00	0.021	0.021
214.75	215.00	Py03	215.00	216.00	P003754	1.00	<0.005	0.001
<b>Pyrite 03%</b>			216.00	217.50	D953317	1.50	<0.005	0.001
2-3% very fine disseminated pyrite along the foliation.			217.50	219.00	D953318	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			219.00	220.50	D953319	1.50	<0.005		0.001
			220.50	222.00	D953321	1.50	<0.005		0.001
			222.00	223.50	D953322	1.50	<0.005		0.001
			223.50	225.00	D953323	1.50	<0.005		0.001
			225.00	226.50	D953324	1.50	0.019		0.019
			226.50	228.00	D953325	1.50	0.006		0.006
			228.00	229.50	D953326	1.50	0.008		0.008
			229.50	231.00	D953327	1.50	0.006		0.006
			231.00	232.00	D953328	1.00	<0.005		0.001
			232.00	233.00	P003756	1.00	<0.005		0.001
			233.00	234.00	P003757	1.00	0.005		0.005
			234.00	235.50	D953329	1.50	<0.005		0.001
			235.50	237.00	D953331	1.50	<0.005		0.001
			237.00	238.50	D953332	1.50	<0.005		0.001
			238.50	240.00	D953333	1.50	<0.005		0.001
			240.00	241.50	D953334	1.50	<0.005		0.001
			241.50	243.00	D953335	1.50	<0.005		0.001
243.00	254.00	Bio; Sil <b>Biotisation; Silicification</b> Dark green-black biotite in the sens of the foliation @ 50° TCA and silicified bands in the same sens.							
243.00	254.00	FOL; FAI <b>Foliation ; Fault</b> High foliation @ 50° TCA. Looks brecciated. Fault? 1% Siliceous fragments in the sens of the foliation.	243.00	244.50	D953336	1.50	<0.005		0.001
			244.50	246.00	D953337	1.50	<0.005		0.001
			246.00	247.00	P003758	1.00	<0.005		0.001
			247.00	248.00	P003759	1.00	0.008		0.008
			248.00	249.00	D953338	1.00	<0.005		0.001
			249.00	250.50	D953339	1.50	<0.005		0.001
			250.50	252.00	D953341	1.50	<0.005		0.001
			252.00	253.50	D953342	1.50	<0.005		0.001
			253.50	255.00	D953343	1.50	0.005		0.005
254.60	291.00	Py01 <b>Pyrite 01%</b> 1% very fine to fine disseminated pyrite. (loc cubic)	255.00	256.50	D953344	1.50	<0.005		0.001
			256.50	258.00	D953346	1.50	<0.005		0.001
			258.00	259.00	P003760	1.00	0.015		0.015
258.60	297.50	FCT; Sil	259.00	260.00	P003761	1.00	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
<b>Fuchsitization; Silicification</b>			260.00	261.00	D953347	1.00	<0.005		0.001
Alternating moderate fuchsitisation and silicification @ 40-50° TCA.			261.00	262.50	D953348	1.50	0.009		0.009
			262.50	264.00	D953349	1.50	0.013		0.013
291-292.65m: High pervasive silicification			264.00	265.50	D953351	1.50	0.034		0.034
			265.50	267.00	D953352	1.50	0.058		0.058
			267.00	268.50	D953353	1.50	0.009		0.009
			268.50	270.00	D953354	1.50	0.026		0.026
			270.00	271.50	D953355	1.50	0.010		0.010
			271.50	273.00	D953356	1.50	0.009		0.009
			273.00	274.50	D953357	1.50	0.006		0.006
			274.50	276.00	D953358	1.50	<0.005		0.001
			276.00	277.50	D953359	1.50	0.008		0.008
			277.50	279.00	D953361	1.50	<0.005		0.001
			279.00	280.50	D953362	1.50	0.006		0.006
			280.50	282.00	D953363	1.50	<0.005		0.001
			282.00	283.50	D953364	1.50	0.005		0.005
			283.50	285.00	D953365	1.50	<0.005		0.001
			285.00	286.50	D953366	1.50	<0.005		0.001
286.20	287.60	S	286.50	288.00	D953367	1.50	0.005		0.005
<b>Sediment (Meta incl.)</b>			288.00	289.00	P003762	1.00	0.076		0.076
Interbedding of black laminations(mm to cm) with beige laminations(mm to cm) @ 30-50° TCA. Homogenous and non magnetic. Folded ?			289.00	290.30	P003763	1.30	0.009		0.009
			290.30	290.80	P003773	0.50	0.038		0.038
Tr very fine disseminated pyrite.			290.80	291.80	P003774	1.00	0.438		0.438
Contacts shapr @ 30-40° TCA.									
291.00	292.65	I2D POR							
<b>Syenite Porphyry Intrusive</b>									
May be just a silicified zone.									
Grey aphanitic matrix with 3-5% white Fp phenos. Non magnetic.									
1-2% white Qz injections and veins @ 40° TCA.									
Brecciated. Matrix silica. 10-20% micro-fractures filled by chlorite.									



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		2% very fine disseminated pyrite.						
		Sharp contacts @ 70-80° TCA.						
291.00	292.65	Py02	291.80	292.80	P003775	1.00	0.192	0.192
		<b>Pyrite 02%</b>	292.80	293.80	P003776	1.00	0.019	0.019
		1-2% very fine to fine disseminated pyrite.	293.80	294.70	P003777	0.90	0.006	0.006
			294.70	296.00	P003764	1.30	0.008	0.008
			296.00	297.00	P003765	1.00	0.009	0.009
			297.00	297.50	P003768	0.50	0.013	0.013
297.50	300.00	I2D POR						
		<b>Syenite Porphyry Intrusive</b>						
		May be just a silicified zone.						
		Same as 291-292.65m.						
297.50	300.00	Sil						
		<b>Silicification</b>						
		High pervasive silicification.						
297.50	300.00	Py02	297.50	298.50	P003769	1.00	0.026	0.026
		<b>Pyrite 02%</b>	298.50	299.50	P003770	1.00	0.329	0.329
		1-3% very fine to fine(loc medium) disseminated pyrite.	299.50	300.00	P003771	0.50	0.177	0.177
300.00		Fin du sondage						
		Nombre d'échantillons : 213						
		Nombre d'échantillons QAQC : 25						
		Longueur totale échantillonnée : 283.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
16.50	16.50	D953185	m	0.00	<0.005	0.001
22.50	22.50	D953190	O54Pa	0.00	3.010	3.010
28.00	28.00	P011284	O53Pb	0.00		
37.50	39.00	D953200	D953199	1.50	<0.005	0.001
52.50	52.50	D953210	O52Pb	0.00	0.337	0.337
66.00	67.50	D953220	D953219	1.50	0.074	0.074
79.50	79.50	D953230	O53Pb	0.00	0.606	0.606
93.50	95.00	D953240	D953239	1.50	0.164	0.164
100.50	100.50	D953245	m	0.00	<0.005	0.001
106.50	106.50	D953250	O54Pa	0.00	2.970	2.970
119.50	121.00	D953260	D953259	1.50	0.020	0.020
135.00	135.00	D953270	O53Pb	0.00	0.601	0.601
148.00	149.00	D953280	D953279	1.00	0.006	0.006
154.50	154.50	D953285	m	0.00	<0.005	0.001
160.50	160.50	D953290	O53Pb	0.00	0.604	0.604
178.50	180.00	D953300	D953299	1.50	0.021	0.021
195.00	195.00	D953310	O54Pa	0.00	2.890	2.890
215.00	215.00	P003755	O52Pb	0.00	0.305	0.305
219.00	220.50	D953320	D953319	1.50	<0.005	0.001
234.00	234.00	D953330	O52Pb	0.00	0.322	0.322
249.00	250.50	D953340	D953339	1.50	<0.005	0.001
255.00	255.00	D953345	m	0.00	<0.005	0.001
262.50	262.50	D953350	O53Pb	0.00	0.592	0.592
276.00	277.50	D953360	D953359	1.50	0.029	0.029
299.50	299.50	P003772	O53Pb	0.00	0.660	0.660

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-63

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie mine

Foré par : Multidrill

Lot :

Décrit par : Geneviève Carignan

Du : 2009-06-07

Date de description : 2009-06-10

Au : 2009-06-13

Collet

Azimut : 325.51°  
 Plongée : -54.00°  
 Longueur : 404.00 m

UTM

Est	629 943.7
Nord	5 374 117.3
Élévation	283.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	62.00	341.75°	-50.90°	Non
Reflex	92.00	343.15°	-49.70°	Non
Reflex	122.00	342.85°	-48.10°	Non
Reflex	152.00	343.25°	-46.50°	Non
Reflex	182.00	344.05°	-45.90°	Non
Reflex	215.00	345.75°	-44.70°	Non
Reflex	245.00	344.15°	-43.00°	Non
Reflex	275.00	345.35°	-41.60°	Non
Reflex	305.00	344.55°	-40.30°	Non
Reflex	335.00	345.65°	-38.80°	Non
Reflex	365.00	346.45°	-37.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

NAD 83, UTM Zone 17

Hole surveyed in November 2009 by Descarreaux.

Resampled (with added comments) by C. Gagnier (Sept 2010).

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	33.40	MT <b>Overburden</b> Driller's note: casing at 34m.							
33.40	46.00	S <b>Sediment (Meta incl.) 25°</b> Medium green-grey, well laminated, homogeneous and schistose, fine grained sandstone ? or ash tuff ? 3% of yellowish sericite shreds.  From the original G. Carignan log:  May be "massive" meta-sediments. Pale green fine grained matrix. Light foliation @ 30° TCA. Homogenous and non magnetic. 1% white Qz veins @ 30-40° TCA. Local light sericitisation along foliation and loc light chloritisation. Tr (loc up to 11%) very fine to fine disseminated pyrite. (loc cubic).							
33.40	62.00	SCH <b>Schistosed 35°</b> Well laminated and schistose. Several kink bends.	33.40	34.80	D506386	1.40	0.008		0.008
			34.80	36.20	D506387	1.40	0.010		0.010
			36.20	37.60	D506388	1.40	0.009		0.009
			37.60	39.00	D506389	1.40	0.010		0.010
			39.00	40.40	D506390	1.40	0.006		0.006
			40.40	41.80	D506391	1.40	0.006		0.006
			41.80	43.20	D506392	1.40	0.009		0.009
			43.20	44.70	D506393	1.50	0.006		0.006
			44.70	46.00	D506394	1.30	0.010		0.010
46.00	152.40	S; RUB <b>Sediment (Meta incl.); Banded</b> Upper contact sharp @ 45° TCA. Dark green bands alternating with beige-pale green bands. Strongly foliated @ 30-50° TCA, fractured and folded. Tr red chert (jasp?) rounded fragments (2-5cm) and siliceous pyritic rounded fragments. Non magnetic. Loc brecciated. Tr white Qz injections. Light to loc moderate chloritisation with light sericitisation and carbonatisation. Loc zones of bleaching. Tr very fine to fine disseminated pyrite and along foliation.  124.9-152.4m: Light foliation @ 30-50° TCA.	46.00	47.00	D506396	1.00	0.008		0.008
			47.00	48.00	D506398	1.00	0.018		0.018
			48.00	49.00	P009366	1.00	0.178		0.178
			49.00	50.00	P009367	1.00	0.016		0.016
			50.00	51.50	D506399	1.50	0.015		0.015
			51.50	53.00	D506400	1.50	0.024		0.024
			53.00	54.50	D506401	1.50	0.023		0.023
			54.50	56.00	D506402	1.50	0.116		0.116
			56.00	57.50	D506403	1.50	0.005		0.005
			57.50	59.00	D506404	1.50	0.131		0.131
59.00	61.70	Blch	59.00	60.50	D506405	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
60.00	60.30	<b>Bleaching</b> Moderate bleaching. VEI;30;QzSr;;60°;Py0.5;	60.50	62.00	D506406	1.50	0.050		0.050
		<b>Vein 30 Quartz Sericite 60° Pyrite0.5%</b> 30 cm white Qz + Se veins with traces of pyrite.							
62.00	66.50	FRC	62.00	63.50	D506407	1.50	0.340		0.340
		<b>Fractured</b> 60-70% broken core.	63.50	65.00	D506408	1.50	0.133		0.133
			65.00	66.50	D506409	1.50	0.233		0.233
66.50	109.20	SCH	66.50	68.00	D506410	1.50	0.010		0.010
		<b>Schistosed 35°</b> Well laminated and schistose.	68.00	69.50	D506411	1.50	0.009		0.009
			69.50	71.00	D506412	1.50	0.006		0.006
			71.00	72.50	D506413	1.50	0.007		0.007
71.70	72.20	Blich	72.50	74.00	D506414	1.50	0.077		0.077
		<b>Bleaching</b> Moderate bleaching.	74.00	75.50	D506416	1.50	0.184		0.184
			75.50	77.00	D506418	1.50	0.011		0.011
			77.00	78.00	P009368	1.00	0.097		0.097
			78.00	79.00	P009369	1.00	0.042		0.042
			79.00	80.00	D506419	1.00	0.102		0.102
			80.00	81.50	D506420	1.50	0.012		0.012
			81.50	83.00	D506421	1.50	0.054		0.054
			83.00	84.50	D506422	1.50	0.014		0.014
			84.50	86.00	D506423	1.50	0.050		0.050
			86.00	87.50	D506424	1.50	0.033		0.033
			87.50	89.00	D506425	1.50	0.039		0.039
			89.00	90.50	D506426	1.50	0.006		0.006
			90.50	92.00	D506427	1.50	0.013		0.013
	92.00	93.50	D506428	1.50	0.031		0.031		
	93.50	95.00	D506429	1.50	0.007		0.007		
	95.00	96.50	D506430	1.50	0.026		0.026		
	96.50	98.00	D506431	1.50	0.086		0.086		
	98.00	99.50	D506432	1.50	0.052		0.052		
	99.50	101.00	D506433	1.50	0.067		0.067		
	101.00	102.50	D506434	1.50	0.060		0.060		
	102.50	104.00	D506436	1.50	0.300		0.300		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
115.00	124.70	Py02 <b>Pyrite 02%</b> 1-2% very fine pyrite. Disseminated and along foliation.	104.00	105.50	D506438	1.50	0.030		0.030
			105.50	107.00	D506439	1.50	0.099		0.099
			107.00	108.50	D506441	1.50	0.015		0.015
			108.50	110.00	D506442	1.50	0.026		0.026
			110.00	111.50	D506443	1.50	0.014		0.014
			111.50	113.20	D506444	1.70	0.030		0.030
			113.20	115.00	D506445	1.80	0.012		0.012
			115.00	116.00	P009370	1.00	0.014		0.014
			116.00	117.00	P009371	1.00	0.025		0.025
			117.00	118.00	P009372	1.00	0.005		0.005
			118.00	119.00	P009373	1.00	0.018		0.018
			119.00	120.00	P009374	1.00	<0.005		0.001
			120.00	121.00	P009375	1.00	0.019		0.019
			121.00	122.00	P009376	1.00	0.013		0.013
			122.00	123.00	P009377	1.00	0.008		0.008
			123.00	124.00	P009379	1.00	0.007		0.007
			124.00	125.00	P009380	1.00	0.006		0.006
			125.00	126.50	D506446	1.50	<0.005		0.001
			126.50	128.00	D506447	1.50	0.007		0.007
			128.00	129.50	D506448	1.50	0.005		0.005
129.50	131.00	D506449	1.50	<0.005		0.001			
131.00	132.50	D506450	1.50	<0.005		0.001			
132.50	134.00	D506451	1.50	0.011		0.011			
134.00	135.50	D506452	1.50	0.011		0.011			
135.50	137.00	D506453	1.50	0.007		0.007			
137.00	138.50	D506454	1.50	0.006		0.006			
138.50	140.20	D506456	1.70	0.006		0.006			
140.20	142.00	D506458	1.80	0.008		0.008			
142.00	143.00	P009381	1.00	0.008		0.008			
142.70	144.00	Py02 <b>Pyrite 02%</b> 1-2% very fine to fine disseminated pyrite (loc cubic) and along foliation.	143.00	144.00	P009382	1.00	0.011		0.011
			144.00	145.70	D506459	1.70	0.017		0.017
			145.70	147.50	D506460	1.80	<0.005		0.001
146.70	152.40	V4	147.50	149.00	D506461	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Ultramafic Volcanic (incl. Flows)</b>	149.00	150.40	D506462	1.40	<0.005		0.001
		May be just a high chloritisation.	150.40	151.50	D506463	1.10	<0.005		0.001
		Dark green aphanitic matrix. Very soft, high pervasive chloritisation and light to moderate carbonatisation. Foliation @ 20-30° TCA. Homogenous and non magnetic.							
		Upper contact sharp @ 20-30° TCA, lower contact iis broken.							
151.30	151.80	FAI <b>Fault</b> Fault?	151.50	153.00	D506464	1.50	<0.005		0.001
152.40	404.00	BA <b>Mafic Meta-Volcanic</b>	153.00	154.00	P009383	1.00	0.014		0.014
		Mafic volcanic rock.	154.00	155.00	P009384	1.00	0.015		0.015
		Upper contact sharp @ 30-40° TCA. Grey-greenish fine grained (zones of medium grained matrix) matrix. Light foliation @ 20-30° TCA and non magnetic. Heavy, homogenous. 2-3% small brown minerals (leucoxenes or carbonates?) Tr Cc amygdules (2mm-5mm). Loc cm to mm bands of ultramafics. Loc brecciated. 3-4% graphitic argillite bands along foliation. Tr white Qz±Cc veins @ 60° TCA.	155.00	156.50	D506465	1.50	<0.005		0.001
		Bleached volcanics with loc light sericitisation and chloritisation along foliation and pervasive silicification. Tr-1% very fine to fine pyrite (loc cubic). Disseminated and along foliation. Tr Cp.	156.50	158.00	D506466	1.50	<0.005		0.001
			158.00	159.00	P009385	1.00	<0.005		0.001
			159.00	160.00	P009386	1.00	<0.005		0.001
		EOH: 404m							
152.40	205.60	Car; Ser; Sil <b>Carbonatisation; Sericitisation; Silicification</b>							
		Moderate to high carbonatisation and sericitisation and silicification as injections @ ~10-20° TCA.							
		Moderate silicification at lower contact.							
160.00	169.00	SCH <b>Schistosed 20°</b>	160.00	161.00	P009387	1.00	<0.005		0.001
		Weakly schistose.	161.00	162.50	D506467	1.50	0.008		0.008
			162.50	164.00	D506468	1.50	0.010		0.010
			164.00	165.50	D506469	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			165.50	167.00	D506470	1.50	<0.005		0.001
			167.00	168.50	D506471	1.50	<0.005		0.001
			168.50	170.00	D506472	1.50	0.005		0.005
			170.00	171.50	D506473	1.50	<0.005		0.001
			171.50	173.00	D506474	1.50	<0.005		0.001
			173.00	174.50	D506476	1.50	0.005		0.005
			174.50	176.00	D506478	1.50	0.005		0.005
			176.00	177.50	D506479	1.50	0.023		0.023
			177.50	179.00	D506481	1.50	0.006		0.006
			179.00	180.00	P009388	1.00	0.055		0.055
			180.00	181.00	P009389	1.00	0.159		0.159
			181.00	182.00	P009390	1.00	0.257		0.257
			182.00	183.00	P009391	1.00	0.158		0.158
			183.00	184.00	P009392	1.00	0.086		0.086
			184.00	185.00	P009393	1.00	0.072		0.072
			185.00	186.00	P009394	1.00	0.198		0.198
			186.00	187.00	P009395	1.00	0.012		0.012
			187.00	188.00	P009396	1.00	0.006		0.006
			188.00	189.00	P009397	1.00	<0.005		0.001
			189.00	190.00	P009398	1.00	0.009		0.009
190.00	321.00	SCH	190.00	191.00	P009399	1.00	<0.005		0.001
		<b>Schistosed 20°</b>	191.00	192.50	D506482	1.50	0.005		0.005
		Moderately schistose.	192.50	194.00	D506483	1.50	0.005		0.005
			194.00	195.50	D506484	1.50	<0.005		0.001
			195.50	197.00	D506485	1.50	<0.005		0.001
			197.00	198.50	D506486	1.50	<0.005		0.001
			198.50	200.00	D506487	1.50	<0.005		0.001
			200.00	201.50	D506488	1.50	<0.005		0.001
			201.50	203.00	D506489	1.50	<0.005		0.001
			203.00	204.00	D506490	1.00	<0.005		0.001
			204.00	205.00	D506491	1.00	<0.005		0.001
205.00	210.10	Py02	205.00	206.00	P009400	1.00	<0.005		0.001
		<b>Pyrite 02%</b>	206.00	207.00	P009401	1.00	<0.005		0.001
		1-2% very fine to fine pyrite(loc cubic). Disseminated and along							



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
foliation.	207.00	208.00	P009402	1.00	<0.005		0.001
	208.00	209.00	P009404	1.00	0.020		0.020
	209.00	210.00	P009405	1.00	<0.005		0.001
	210.00	211.00	P009406	1.00	0.005		0.005
	211.00	212.00	P009407	1.00	<0.005		0.001
	212.00	213.50	D506492	1.50	<0.005		0.001
	213.50	215.00	D506493	1.50	<0.005		0.001
	215.00	216.50	D506494	1.50	<0.005		0.001
	216.50	218.00	D506496	1.50	<0.005		0.001
	218.00	219.50	D506498	1.50	<0.005		0.001
	219.50	221.00	D506499	1.50	<0.005		0.001
	221.00	222.50	D506500	1.50	<0.005		0.001
	222.50	224.00	D506501	1.50	0.005		0.005
	224.00	225.50	D506502	1.50	0.005		0.005
	225.50	227.00	D506503	1.50	<0.005		0.001
	227.00	228.50	D506504	1.50	<0.005		0.001
	228.50	230.00	D506505	1.50	0.005		0.005
	230.00	231.00	P009408	1.00	<0.005		0.001
	231.00	232.00	P009409	1.00	<0.005		0.001
	232.00	233.00	D506506	1.00	0.006		0.006
	233.00	234.50	D506507	1.50	<0.005		0.001
	234.50	236.00	D506508	1.50	<0.005		0.001
	236.00	237.50	D506509	1.50	0.005		0.005
	237.50	239.00	D506510	1.50	<0.005		0.001
	239.00	240.50	D506511	1.50	<0.005		0.001
	240.50	242.00	D506512	1.50	<0.005		0.001
	242.00	243.50	D506513	1.50	<0.005		0.001
	243.50	245.00	D506514	1.50	<0.005		0.001
	245.00	246.50	D506516	1.50	0.305		0.305
	246.50	248.00	D506518	1.50	0.005		0.005
248.00	249.50	D506519	1.50	0.028		0.028	
249.50	251.00	D506520	1.50	<0.005		0.001	
251.00	252.50	D506521	1.50	<0.005		0.001	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			252.50	254.00	D506522	1.50	<0.005		0.001
			254.00	255.50	D506523	1.50	<0.005		0.001
			255.50	257.00	D506524	1.50	<0.005		0.001
			257.00	258.50	D506525	1.50	<0.005		0.001
			258.50	260.00	D506526	1.50	<0.005		0.001
			260.00	261.50	D506527	1.50	<0.005		0.001
			261.50	263.00	D506528	1.50	<0.005		0.001
			263.00	264.50	D506529	1.50	<0.005		0.001
			264.50	266.00	D506530	1.50	<0.005		0.001
			266.00	267.50	D506531	1.50	<0.005		0.001
			267.50	269.00	D506532	1.50	<0.005		0.001
			269.00	270.50	D506533	1.50	<0.005		0.001
			270.50	272.00	D506534	1.50	0.005		0.005
			272.00	273.50	D506536	1.50	<0.005		0.001
			273.50	275.00	D506538	1.50	<0.005		0.001
			275.00	276.50	D506539	1.50	<0.005		0.001
			276.50	278.00	D506541	1.50	<0.005		0.001
			278.00	279.50	D506542	1.50	0.005		0.005
			279.50	281.00	D506543	1.50	<0.005		0.001
			281.00	282.50	D506544	1.50	<0.005		0.001
			282.50	284.00	D506545	1.50	<0.005		0.001
			284.00	285.00	D506546	1.00	<0.005		0.001
			285.00	286.00	P009410	1.00	<0.005		0.001
285.20	285.50	VEI;30;QzCcSr;;30°;; <b>Vein 30 Quartz Calcite Sericite 30°</b> 30 cm Qz-Cc±Sr vein @ 30° TCA.							
285.50	287.00	S <b>Sediment (Meta incl.)</b> Black-dark green aphanitic matrix foliated @ 30-40° TCA. Homogenous and non magnetic.  Light carbonatisation in injections and veins @ 30° TCA.  Tr very fine disseminated pyrite.  Upper contact sharp @ 30° TCA and lower contact is broken.	286.00	287.00	P009411	1.00	0.005		0.005
			287.00	288.50	D506547	1.50	0.005		0.005
			288.50	290.00	D506548	1.50	<0.005		0.001
			290.00	291.50	D506549	1.50	0.005		0.005
			291.50	293.00	D506550	1.50	<0.005		0.001
			293.00	294.50	D506551	1.50	0.005		0.005
			294.50	296.00	D506552	1.50	<0.005		0.001
			296.00	297.50	D506553	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
305.55	311.10	I2J <b>Diorite</b> Diorite or medium grained andesite/basalt.	297.50	299.00	D506554	1.50	<0.005		0.001
			299.00	300.50	D506556	1.50	<0.005		0.001
			300.50	302.00	D506558	1.50	<0.005		0.001
			302.00	303.50	D506559	1.50	<0.005		0.001
			303.50	305.00	D506560	1.50	<0.005		0.001
			305.00	306.50	D506561	1.50	<0.005		0.001
			306.50	308.00	D506562	1.50	<0.005		0.001
			308.00	309.50	D506563	1.50	0.005		0.005
			309.50	311.00	D506564	1.50	0.007		0.007
			311.00	312.50	D506565	1.50	0.010		0.010
			312.50	314.00	D506566	1.50	<0.005		0.001
			314.00	315.50	D506567	1.50	<0.005		0.001
			315.50	317.00	D506568	1.50	<0.005		0.001
			317.00	318.50	D506569	1.50	0.005		0.005
			318.50	320.00	D506570	1.50	<0.005		0.001
320.50	322.10	Py02 <b>Pyrite 02%</b> 2-3% pyrite and 1-2% pyrrhotite in stringers and along foliation and disseminated associated with ultramafics injections.	320.00	321.00	P009412	1.00	0.006		0.006
			321.00	322.00	P009413	1.00	0.005		0.005
			322.00	323.00	P009414	1.00	<0.005		0.001
			323.00	324.50	D506571	1.50	<0.005		0.001
			324.50	326.00	D506572	1.50	<0.005		0.001
			326.00	327.50	D506573	1.50	<0.005		0.001
			327.50	329.00	D506574	1.50	<0.005		0.001
			329.00	330.50	D506576	1.50	<0.005		0.001
			330.50	332.00	D506578	1.50	<0.005		0.001
			332.00	333.50	D506579	1.50	<0.005		0.001
			333.50	335.00	D506581	1.50	<0.005		0.001
			335.00	336.00	D506582	1.00	0.006		0.006
			336.00	337.00	D506583	1.00	<0.005		0.001
			337.00	338.00	P009415	1.00	<0.005		0.001
			338.00	339.00	P009416	1.00	<0.005		0.001
338.70	338.80	VEI;10;Qz;;45°;Py30; <b>Vein 10 Quartz 45° Pyrite30%</b> 10 cm white quartz vein with 30% Pyrite @ 45° TCA.	339.00	340.00	P009417	1.00	<0.005		0.001
			340.00	341.00	D506584	1.00	<0.005		0.001
			341.00	342.50	D506585	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
346.45	346.65	VEI;20;Qz;;45°; <b>Vein 20 Quartz 45°</b> 20 cm white Qz vein @ 40-50° TCA.	342.50	344.00	D506586	1.50	<0.005		0.001
			344.00	345.50	D506587	1.50	<0.005		0.001
			345.50	347.00	D506588	1.50	0.006		0.006
			347.00	348.50	D506589	1.50	<0.005		0.001
			348.50	350.00	D506590	1.50	<0.005		0.001
			350.00	351.50	D506591	1.50	<0.005		0.001
			351.50	353.00	D506592	1.50	<0.005		0.001
			353.00	354.50	D506593	1.50	<0.005		0.001
			354.50	356.00	D506594	1.50	<0.005		0.001
			356.00	357.50	D506596	1.50	<0.005		0.001
			357.50	359.00	D506598	1.50	<0.005		0.001
			359.00	360.50	D506599	1.50	<0.005		0.001
			360.50	362.00	D506600	1.50	<0.005		0.001
			362.00	363.00	D506601	1.00	<0.005		0.001
			363.00	364.00	D506602	1.00	<0.005		0.001
363.20	365.30	BRE <b>Breccia</b> Breccia. Pale green medium grained rounded to angular fragments (aligned @ 30-40° TCA) in a dark green-black aphanitic matrix. 1% pyrite (loc cubic) disseminated.	364.00	365.00	P009418	1.00	<0.005		0.001
			365.00	366.00	P009419	1.00	0.006		0.006
			366.00	367.00	P009421	1.00	<0.005		0.001
			367.00	368.00	P009422	1.00	<0.005		0.001
			368.00	369.50	D506603	1.50	<0.005		0.001
367.70	367.80	VEI;10;QzCc;;35°;Py02; <b>Vein 10 Quartz Calcite 35° Pyrite02%</b> 10 cm smokey Qz-Cc vein with 1-2% pyrite mostly at borders.	369.50	371.00	D506604	1.50	<0.005		0.001
			371.00	372.50	D506605	1.50	<0.005		0.001
			372.50	374.00	D506606	1.50	<0.005		0.001
371.90	384.20	Py03 <b>Pyrite 03%</b> 2-3% medium grained pyrite. Disseminated and in blebs and clusters associated with graphitic argillite.	374.00	375.50	D506607	1.50	0.007		0.007
			375.50	377.00	D506608	1.50	<0.005		0.001
			377.00	378.00	P009423	1.00	<0.005		0.001
			378.00	379.00	P009424	1.00	0.010		0.010
			379.00	380.00	P009425	1.00	0.006		0.006
			380.00	381.00	P009426	1.00	<0.005		0.001
			381.00	382.00	P009427	1.00	0.017		0.017
			382.00	383.00	P009428	1.00	<0.005		0.001
			383.00	384.00	P009429	1.00	<0.005		0.001
			384.00	385.50	D506609	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
391.55	392.20	VEI;65;QzCcCl;;Py01Cp0.5Po0.5; <b>Vein 65 Quartz Calcite Chlorite Pyrite01% Chalcopyrite0.5% Pyrrhotite0.5%</b> White Qz-Cc±Cl vein with Tr of chalcopyrite and pyrrhotite chunk(Po and Cp associated) and 1% pyrite (mostly at borders).  Upper contact @ 50° TCA and lower 10° TCA.	385.50	386.80	D506610	1.30	<0.005		0.001
			386.80	388.20	D506611	1.40	<0.005		0.001
			388.20	389.50	D506612	1.30	<0.005		0.001
			389.50	391.00	D506613	1.50	<0.005		0.001
			391.00	392.00	P009430	1.00	<0.005		0.001
			392.00	393.00	P009431	1.00	<0.005		0.001
			393.00	394.00	D506614	1.00	<0.005		0.001
			394.00	395.00	D506616	1.00	<0.005		0.001
			395.00	396.50	D506618	1.50	<0.005		0.001
			396.50	398.00	D506619	1.50	<0.005		0.001
			398.00	399.50	D506620	1.50	0.005		0.005
			399.50	401.00	D506621	1.50	0.005		0.005
			401.00	402.50	D506622	1.50	<0.005		0.001
			402.50	404.00	D506623	1.50	<0.005		0.001
404.00	Fin du sondage Nombre d'échantillons : 273 Nombre d'échantillons QAQC : 31 Longueur totale échantillonnée : 370.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
46.00	47.00	D506397	D506396	1.00	0.018	0.018
46.00	46.00	D506395	O61d	0.00	5.130	5.130
74.00	74.00	D506415	O52Pb	0.00	0.303	0.303
74.00	75.50	D506417	D506416	1.50	0.109	0.109
102.50	102.50	D506435	O53Pb	0.00	0.616	0.616
102.50	104.00	D506437	D506436	1.50	0.355	0.355
107.00	107.00	D506440	m	0.00	<0.005	0.001
123.00	123.00	P009378	O52Pb	0.00	0.330	0.330
138.50	138.50	D506455	O54Pa	0.00	3.140	3.140
138.50	140.20	D506457	D506456	1.70	0.006	0.006
173.00	173.00	D506475	O61d	0.00	5.090	5.090
173.00	174.50	D506477	D506476	1.50	<0.005	0.001
177.40	177.40	D506480	m	0.00	<0.005	0.001
208.00	208.00	P009403	O53Pb	0.00	0.657	0.657
216.50	218.00	D506497	D506496	1.50	<0.005	0.001
216.50	216.50	D506495	O52Pb	0.00	0.310	0.310
245.00	245.00	D506515	O53Pb	0.00	0.601	0.601
245.00	246.50	D506517	D506516	1.50	<0.005	0.001
272.00	272.00	D506535	O54Pa	0.00	2.940	2.940
272.00	273.50	D506537	D506536	1.50	<0.005	0.001
276.50	276.50	D506540	m	0.00	<0.005	0.001
299.00	300.50	D506557	D506556	1.50	<0.005	0.001
299.00	299.00	D506555	O61d	0.00	5.030	5.030
329.00	329.00	D506575	O52Pb	0.00	0.338	0.338
329.00	330.50	D506577	D506576	1.50	<0.005	0.001
333.50	333.50	D506580	m	0.00	<0.005	0.001
356.00	356.00	D506595	O53Pb	0.00	0.711	0.711
356.00	357.50	D506597	D506596	1.50	<0.005	0.001
366.00	366.00	P009420	O54Pa	0.00	2.990	2.990
394.00	395.00	D506617	D506616	1.00	<0.005	0.001
394.00	394.00	D506615	O54Pa	0.00	3.160	3.160

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-64	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail :
Foré par : MultiDrill	Lot :	
Décrit par : H.Tazerout	Du : 2009-06-19	Date de description : 2009-06-20
	Au : 2009-06-20	

Collet

Azimut : 139.19°  
 Plongée : -51.60°  
 Longueur : 123.00 m

UTM

Est	630 022.3
Nord	5 374 531.5
Élévation	279.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	45.00	307.00°	-51.00°	Oui
Reflex	45.00	307.00°	-51.00°	Oui
Reflex	75.00	153.40°	-49.50°	Non
Reflex	105.00	154.40°	-48.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

NAD 83, UTM Zone 17  
 Resampled Sept 17, 2010 by K.Wallace  
 \*\*indicates changes made

Dimension de la carotte : NQ Cimenté : Non Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	33.00	MT <b>Casing</b> casing							
33.00	56.50	BA; FOL <b>Mafic Meta-Volcanic ; Foliation</b> Dark green to green to grayish green to grey, fine to medium grain, highly foliated@40-50°TCA. 3-5% moderately to highly bleached sections<60.0cm. 1-2% irregular white Alb+/-++ V1Qtz-Carb<3.0cm mainly along the foliation. Tr fine diss Py up to 2-3% Py bands<2.0cm along foliation. Lower Contact@40°TCA.	33.50	35.00	P008622	1.50	0.015		0.015
			35.00	36.00	P008623	1.00	0.219		0.219
			36.00	37.50	P008625	1.50	0.014		0.014
			37.50	39.00	P008626	1.50	<0.005		0.001
			39.00	40.50	P008627	1.50	0.019		0.019
			40.50	42.00	P008628	1.50	0.076		0.076
			42.00	43.50	P008629	1.50	0.006		0.006
			43.50	45.00	P008630	1.50	0.125		0.125
			45.00	46.50	P008631	1.50	<0.005		0.001
			46.50	48.00	P008632	1.50	0.010		0.010
			48.00	49.50	P008633	1.50	0.007		0.007
			49.50	51.00	P008634	1.50	0.202		0.202
			51.00	52.50	P008635	1.50	0.007		0.007
			52.50	54.00	P008636	1.50	0.007		0.007
			54.00	55.20	P011100	1.20	0.010		0.010
			55.20	56.50	P011101	1.30	2.120		2.120
56.50	72.60	TZ; TZ; FOL; BX <b>Transitionnel Zone; Transitionnel Zone; Foliation ; Breccia</b> light green to dark grey, highly foliated@40°TCA & highly hydro-brecciated cemented by a grey-smokey cherty silca fluid mainly Alb+/-+++ 5-7% buff greenish yellow Ser+/-+++ 3-5% light green to dark green Chl+/- & Loc apple green Ep+/-+. 5% very fine to fine diss Py. Upper Contact@40°TCA & Lower Contact@40°TCA.	56.50	58.00	P011102	1.50	2.460		2.460
			58.00	59.00	P011103	1.00	2.480		2.480
			59.00	60.00	P011104	1.00	2.650		2.650
			60.00	61.00	P011105	1.00	1.570		1.570
			61.00	62.00	P011106	1.00	1.355		1.355
			62.00	63.00	P011107	1.00	1.010		1.010
			63.00	64.00	P011108	1.00	1.785		1.785
			64.00	65.00	P011109	1.00	1.440		1.440
			65.00	66.00	P011110	1.00	1.435		1.435
			66.00	67.00	P011111	1.00	0.888		0.888
			67.00	68.00	P011112	1.00	1.505		1.505
			68.00	69.00	P011114	1.00	1.335		1.335
			69.00	70.00	P008637	1.00	1.910		1.910
			70.00	71.00	P008638	1.00	1.180		1.180
			71.00	72.00	P008639	1.00	0.982		0.982



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
72.60	114.00	<p>SY POR</p> <p><b>Syenite Porphyry Intrusive</b></p> <p>Red brisk to wine red with loc. a light orange hue, medium grain matrix, 3-5% euhedral phenos&lt;1.0cm mainly Alb++ or Chl+/+++ &amp; loc lath phenos &lt;0.5cm wide &amp; &lt;2.0cm long. highly fractured &amp; filled with a white Alb++ silica-carb fluid or by a dark green Chl. 3-5% white to smokey Alb+/+++ VIQtz-Carb (tension fillings)@30-50°TCA&lt;2.0cm. 2-3% Chl+/+++ . Loc. buff greenish yellow Ser+/+. 2-3% extremely fine to fine diss Py up to loc 7-10% Py &amp; Tr fine diss Cp &amp; Cp chunks&lt;1.0cm Loc. Hs along the contacts of the VIQtz-Carb.. Upper Contact@40°TCA.</p>	72.00	73.00	P008640	1.00	0.750		0.750
			73.00	74.00	P008641	1.00	0.893		0.893
			74.00	75.00	P008642	1.00	0.103		0.103
			75.00	76.00	P008643	1.00	0.218		0.218
			76.00	77.00	P008644	1.00	0.060		0.060
			77.00	78.00	P008645	1.00	0.467		0.467
			78.00	79.00	P008646	1.00	0.456		0.456
			79.00	80.00	P008647	1.00	1.225		1.225
			80.00	81.00	P008648	1.00	0.100		0.100
			81.00	82.00	P008649	1.00	0.116		0.116
			82.00	83.00	P008650	1.00	0.066		0.066
			83.00	84.00	P008651	1.00	0.115		0.115
			84.00	85.00	P008652	1.00	0.279		0.279
			85.00	86.00	P008653	1.00	0.195		0.195
			86.00	87.00	P008654	1.00	0.029		0.029
			87.00	88.00	P008655	1.00	0.013		0.013
			88.00	89.00	P008657	1.00	0.072		0.072
			89.00	90.00	P008658	1.00	0.145		0.145
			90.00	91.00	P008659	1.00	0.064		0.064
			91.00	92.00	228857	1.00	0.127		0.127
92.00	93.00	228858	1.00	0.057		0.057			
93.00	94.00	228859	1.00	0.190		0.190			
94.00	95.00	228861	1.00	0.181		0.181			
94.90	100.60	<p>I2D POR; FRA; BX</p> <p><b>Syenite Porphyry Intrusive; Fractured; Breccia</b></p> <p>Same as main description, but highly fractured &amp; filled with a white-smokey cherty Alb+/+++ Silica-Carb fluid, highly Silicified &amp; highly hydro-brecciated cemented by white-smokey cherty Alb+/+++ Silica-Carb fluid. 7-10% extremely fine to fine diss Py.</p>							
			95.00	96.00	228862	1.00	1.450		1.450
			96.00	97.00	228863	1.00	1.740		1.740
			97.00	98.00	228865	1.00	1.805		1.805
			98.00	99.00	228866	1.00	2.870		2.870
94.90	109.20	<p>Py8.5</p> <p><b>Pyrite 8.5%</b></p> <p>Same as the 94.90-100.60m sub lithology description &amp; same as the 100.60-103.50m alteration description 7 same as the main description from 103.50m.</p>	99.00	100.00	228867	1.00	2.730		2.730

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
100.60	103.50	Pot50 <b>Potassic alteration 50</b> Red with a light to medium orange hue. 7-10% extremely fine to fine diss Py.	100.00	101.00	228868	1.00	2.020		2.020
			101.00	102.00	228869	1.00	1.340		1.340
			102.00	103.00	228870	1.00	1.300		1.300
			103.00	104.00	228871	1.00	1.155		1.155
			104.00	105.00	228872	1.00	1.430		1.430
			105.00	106.00	228873	1.00	1.485		1.485
			106.00	107.00	228874	1.00	2.140		2.140
			107.00	108.00	228875	1.00	2.350		2.350
			108.00	109.00	P008660	1.00	3.950		3.950
			109.00	110.00	P008661	1.00	0.687		0.687
			110.00	111.00	P008662	1.00	0.017		0.017
			111.00	112.00	P008663	1.00	0.463		0.463
			112.00	113.00	P008664	1.00	0.626		0.626
113.00	114.00	P008665	1.00	0.367		0.367			
114.00	123.00	TZ; FOL <b>Transitionnel Zone; Foliation</b> Light green to dark green, mediumly grained, highly foliated to weakly-moderately sheared@40°TCA. 5-7% white-smokey Alb+ irregular V1Qtz-Carb@10-60°TCA<4.0cm. Buff greenish yellow Ser++ overall. 25% Chl+++ "phenos"? or Chl chunks highly elongated along foliation<2.0cm long & <0.5cm wide. Tr-15 fine diss Py to Py cubes<0.5cm & tr fine diss AsPy & AsPy cubes <0.4cm. Upper Contact@40°TCA. E.O.H.: 123.00m due to a drift.							
114.00	123.00	CIS <b>Sheared</b> weak to moderate shearing at 40-50 DTCA. Phenos are elongate and completely chlorite replaced. Abundant sericite laths present.	114.00	115.00	P008666	1.00	0.105		0.105
			115.00	116.00	P008667	1.00	0.060		0.060
			116.00	117.00	P008668	1.00	0.027		0.027
			117.00	118.00	P008669	1.00	0.094		0.094
			118.00	119.00	P008670	1.00	0.241		0.241
			119.00	120.00	P008671	1.00	0.147		0.147
			120.00	121.00	P008673	1.00	0.013		0.013
			121.00	122.00	P008674	1.00	0.109		0.109
			122.00	123.00	P008675	1.00	0.021		0.021

123.00

Fin du sondage

Nombre d'échantillons : 82

Nombre d'échantillons QAQC : 6

Longueur totale échantillonnée : 89.50

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
35.00	35.00	P008624	O53Pb	0.00	0.639	0.639
67.00	67.00	P011113	O54Pa	0.00	2.860	2.860
87.00	87.00	P008656	O54Pa	0.00	2.890	2.890
93.00	94.00	228860	228859	1.00	0.191	0.191
96.00	96.00	228864	O54Pa	0.00	2.910	2.910
119.00	119.00	P008672	O52Pb	0.00	0.320	0.320

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-65

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail :

Foré par :

Lot :

Décrit par : Aidamir Cheroukh

Du : 2009-06-15

Date de description : 2009-06-19

Au : 2009-06-19

Collet

Azimut : 316.90°  
 Plongée : -53.00°  
 Longueur : 338.60 m

UTM

Est	630 038.1
Nord	5 374 511.7
Élévation	280.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	51.00	318.15°	-53.40°	Non
Reflex	81.00	320.65°	-51.80°	Oui
Reflex	111.00	318.75°	-50.50°	Non
Reflex	141.00	321.25°	-48.70°	Non
Reflex	231.00	323.55°	-46.20°	Non
Reflex	261.00	324.05°	-44.80°	Non
Reflex	291.00	324.05°	-43.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

Resampled by Moustapha Seck 17/09/2010

UTM NAD 83 Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	43.60	MT <b>Casing</b> overburden							
43.60	338.60	BA; FOL; AMY <b>Mafic Meta-Volcanic ; Foliation ; Amygdalaire</b> greenish to light grey loc.light-dark green, med. gnd, loc.+/+++ foliated@20-50°TCA, loc. +/+++ bleached, loc. +/++ seric, loc. hydro-brecciated with carb&silica matrix, 1-5% cm-cm amygdules, Tr. of diss.Py with concentrations up to 10% of finely diss. Py with 1-5% diss. Cp associated to bleached, silicified&brecciated zones, loc. gabbroic texture, loc. 1-3%coarse cubic to patchy Py, Tr. of diss. Cp loc., 15-20% leucoxene loc. Hole stopped @338.6m	43.60	44.45	79821	0.85	0.006		0.006
44.45	54.80	Blch; Sil; Alb; Pot <b>Bleaching; Silicification; Albitisation; Potassic alteration</b> dark to greenish grey, mod-high. silicified, loc. hydro-brecciated with Qtz-Carb matrix, mod-highly bleached, loc. chlorite filled microfractures, 1-3% Qtz-Carb injections +/++ alb., +/+++ K-altered, 10-15% diss-Py stringers with 1-5% diss. Cp							
44.45	54.80	Py10; Cp03 <b>Pyrite 10%; Chalcopyrite 03%</b> dark to greenish grey, licified, loc. hydro-brecciated with Qtz-Carb matrix, mod-highly bleached, loc. chlorite filled microfractures, 1-3% Qtz-Carb injections +/++ alb., +/+++ K-altered, loc. 10-15% finely diss.Py with 1-5% diss. Cp loc. in form of stringers/p>	44.45	45.45	79822	1.00	0.020		0.020
			45.45	46.45	79823	1.00	1.070		1.070
			46.45	47.45	79824	1.00	0.058		0.058
46.50	53.70	BX <b>Breccia</b> hydro- brecciated to locally microfractured with loc. chloritic fillings, Qtz-Carb matrix, mod-highly bleached, up to 10-15% diss. Py&1-5% diss. Cp, angular-sub-rounded fragments	47.45	48.45	79825	1.00	0.873		0.873
			48.45	49.45	79826	1.00	0.977		0.977
			49.45	50.45	79827	1.00	2.060		2.060
			50.45	51.45	79828	1.00	11.350	11.35	11.350
			51.45	52.45	79829	1.00	4.920	4.81	4.810
			52.45	53.45	79830	1.00	1.960		1.960
			53.45	54.45	79831	1.00	5.400	5.27	5.270
			54.45	55.45	79832	1.00	0.010		0.010
54.60	89.00	FOL <b>Foliation 30°</b> strongly foliated to sheared@30°TCA, 1% broken core	55.45	56.45	79833	1.00	<0.005		0.001
			56.45	57.50	79834	1.05	<0.005		0.001
			57.50	58.50	D953368	1.00	0.005		0.005



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
106.00	133.20	FOL <b>Foliation 30°</b> mod-strongly foliated@30-50°TCA	105.00	106.50	D953405	1.50	<0.005		0.001
			106.50	107.50	D953406	1.00	<0.005		0.001
			107.50	109.00	79837	1.50	<0.005		0.001
			109.00	110.00	D953407	1.00	<0.005		0.001
			110.00	111.00	D953408	1.00	<0.005		0.001
			111.00	112.50	D953409	1.50	<0.005		0.001
			112.50	114.00	D953411	1.50	<0.005		0.001
			114.00	115.50	D953412	1.50	<0.005		0.001
			115.50	117.00	D953413	1.50	<0.005		0.001
			117.00	118.50	D953414	1.50	<0.005		0.001
			118.50	120.00	D953415	1.50	<0.005		0.001
			120.00	121.50	D953416	1.50	<0.005		0.001
			121.50	123.00	D953417	1.50	<0.005		0.001
			123.00	123.90	D953418	0.90	<0.005		0.001
			123.90	125.40	79838	1.50	<0.005		0.001
			125.40	127.00	D953419	1.60	<0.005		0.001
			127.00	128.00	D953421	1.00	<0.005		0.001
			128.00	129.00	D953422	1.00	<0.005		0.001
			129.00	130.50	D953423	1.50	0.005		0.005
			130.50	132.00	D953424	1.50	<0.005		0.001
132.00	133.00	D953425	1.00	<0.005		0.001			
133.00	133.90	D953426	0.90	0.005		0.005			
133.90	134.80	79839	0.90	<0.005		0.001			
134.00	134.80	VEI;80;QzCl;;20°;; <b>Vein 80 Quartz Chlorite 20°</b> chlorite filled microfractures, +alb	134.80	136.50	D953427	1.70	0.005		0.005
			136.50	138.00	D953428	1.50	<0.005		0.001
			138.00	139.50	D953429	1.50	0.006		0.006
			139.50	141.00	D953431	1.50	<0.005		0.001
140.00	143.00	FRC <b>Fractured</b> 1-5% broken core	141.00	142.70	D953432	1.70	<0.005		0.001
			142.70	143.70	79842	1.00	<0.005		0.001
143.70	144.55	BX <b>Breccia</b> silica-carb microfractured to hydro-brecciated with 1-2% cubic Py	143.70	144.70	79843	1.00	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
143.80	144.80	Py03 <b>Pyrite 03%</b> 1-3% coarse Py to cubic loc. blebs to patches along foliation	144.70	146.20	79844	1.50	<0.005		0.001
145.80	146.30	Blch <b>Bleaching</b> light green, chlorite filled microfractures	146.20	147.50	D953433	1.30	<0.005		0.001
147.00	156.00	FRC <b>Fractured</b> 1-5% broken core							
147.50	148.45	VEI;95;QzCl;;10°;Py01; <b>Vein 95 Quartz Chlorite 10° Pyrite01%</b> Tr-1% diss. Py, chlorite filled microfractures@10°TCA to loc. along CA	147.50	148.50	79845	1.00	<0.005		0.001
			148.50	150.00	D953434	1.50	<0.005		0.001
			150.00	151.50	D953435	1.50	<0.005		0.001
			151.50	153.00	D953436	1.50	<0.005		0.001
			153.00	154.50	D953437	1.50	<0.005		0.001
			154.50	156.00	D953438	1.50	<0.005		0.001
			156.00	157.00	D953439	1.00	<0.005		0.001
			157.00	158.20	D953441	1.20	0.005		0.005
158.20	158.80	VEI;60;QzCc;;40°;Py02; <b>Vein 60 Quartz Calcite 40° Pyrite02%</b> partially Qtz-Carb injected@40°TCA with 1-3% coarse to Py blebs to cubic	158.20	159.20	79846	1.00	<0.005		0.001
			159.20	160.50	D953442	1.30	<0.005		0.001
			160.50	162.00	D953443	1.50	<0.005		0.001
			162.00	163.30	D953444	1.30	<0.005		0.001
			163.30	164.00	79847	0.70	<0.005		0.001
			164.00	165.00	D953446	1.00	<0.005		0.001
			165.00	166.50	D953447	1.50	<0.005		0.001
			166.50	168.00	D953448	1.50	<0.005		0.001
			168.00	169.50	D953449	1.50	<0.005		0.001
			169.50	170.40	D953451	0.90	<0.005		0.001
170.40	171.25	BX <b>Breccia</b> tecto-breccia, chloritic matrix, sub-angular fragments							
170.40	176.60	Py02 <b>Pyrite 02%</b> loc. tecto-brecciated, 1-3% coarse-subcubic Py associated to Qtz-Carb injections	170.40	171.40	79848	1.00	<0.005		0.001
			171.40	172.40	79849	1.00	<0.005		0.001
			172.40	173.30	79850	0.90	<0.005		0.001
			173.30	174.00	79851	0.70	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
183.00	186.00	Py02 <b>Pyrite 02%</b> coarse-subcubic to cm Py patches, loc. microfractured to brecciated	174.00	175.50	79852	1.50	<0.005		0.001
			175.50	177.00	D953452	1.50	<0.005		0.001
			177.00	178.50	D953453	1.50	<0.005		0.001
			178.50	180.00	D953454	1.50	<0.005		0.001
			180.00	181.50	D953455	1.50	<0.005		0.001
			181.50	183.00	D953456	1.50	<0.005		0.001
			183.00	184.50	79853	1.50	<0.005		0.001
			184.50	186.00	79854	1.50	<0.005		0.001
			186.00	187.50	D953457	1.50	<0.005		0.001
			187.50	189.00	D953458	1.50	0.019		0.019
			189.00	190.50	D953459	1.50	<0.005		0.001
			190.50	192.00	D953461	1.50	0.007		0.007
			192.00	193.50	D953462	1.50	<0.005		0.001
			193.50	195.00	D953463	1.50	<0.005		0.001
			195.00	196.50	D953464	1.50	<0.005		0.001
			196.50	198.00	D953465	1.50	<0.005		0.001
			198.00	199.50	D953466	1.50	<0.005		0.001
			199.50	201.00	D953467	1.50	<0.005		0.001
			201.00	202.50	D953468	1.50	<0.005		0.001
			202.50	204.00	D953469	1.50	<0.005		0.001
			204.00	205.50	D953470	1.50	<0.005		0.001
			205.50	207.00	D953471	1.50	0.012		0.012
			207.00	208.50	D953472	1.50	<0.005		0.001
			208.50	210.00	D953473	1.50	0.009		0.009
			210.00	211.50	D953474	1.50	<0.005		0.001
			211.50	213.00	D953475	1.50	<0.005		0.001
213.00	214.00	79855	1.00	<0.005		0.001			
214.00	215.50	D953476	1.50	<0.005		0.001			
215.50	217.00	D953477	1.50	<0.005		0.001			
217.00	218.20	79856	1.20	<0.005		0.001			
218.20	219.00	D953478	0.80	<0.005		0.001			
219.00	220.00	D953479	1.00	<0.005		0.001			
220.00	221.00	D953481	1.00	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			221.00	222.00	79857	1.00	<0.005		0.001
			222.00	223.50	D953482	1.50	<0.005		0.001
			223.50	225.00	D953483	1.50	<0.005		0.001
			225.00	226.50	D953484	1.50	<0.005		0.001
			226.50	228.00	D953486	1.50	<0.005		0.001
			228.00	229.50	D953487	1.50	<0.005		0.001
			229.50	231.00	D953488	1.50	<0.005		0.001
			231.00	232.50	D953489	1.50	<0.005		0.001
			232.50	234.00	D953491	1.50	<0.005		0.001
			234.00	235.50	D953492	1.50	<0.005		0.001
			235.50	237.00	D953493	1.50	<0.005		0.001
236.75	236.90	VEI;15;QzCbCl;30°; <b>Vein 15 Quartz Carbonate Chlorite 30°</b> loc. chlorite filled microfractures	237.00	238.50	D953494	1.50	<0.005		0.001
			238.50	240.00	D953495	1.50	<0.005		0.001
			240.00	241.50	D953496	1.50	0.005		0.005
			241.50	243.00	D953497	1.50	<0.005		0.001
241.55	241.70	VEI;15;QzCbCl;40°; <b>Vein 15 Quartz Carbonate Chlorite 40°</b> loc. chlorite filled microfractures	243.00	244.00	D953498	1.00	<0.005		0.001
			244.00	245.20	D953499	1.20	<0.005		0.001
			245.20	246.20	79858	1.00	<0.005		0.001
			246.20	247.20	79859	1.00	<0.005		0.001
			247.20	248.20	D953501	1.00	0.006		0.006
			248.20	249.00	D953502	0.80	<0.005		0.001
			249.00	250.50	D953503	1.50	<0.005		0.001
			250.50	252.00	D953504	1.50	0.005		0.005
			252.00	253.50	D953505	1.50	0.005		0.005
			253.50	255.00	D953506	1.50	<0.005		0.001
			255.00	256.50	D953507	1.50	<0.005		0.001
			256.50	258.00	D953508	1.50	<0.005		0.001
			258.00	259.50	D953509	1.50	0.005		0.005
			259.50	261.00	D953511	1.50	0.008		0.008
			261.00	262.50	D953512	1.50	<0.005		0.001
			262.50	263.70	79861	1.20	<0.005		0.001
			263.70	265.00	D953513	1.30	<0.005		0.001
			265.00	266.00	D953514	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
266.85	267.00	VEI;15;QzCl;;50°;; <b>Vein 15 Quartz Chlorite 50°</b> smokey to white Qtz-Carb injection, ++/+++ K-altered, loc. chloritized	266.00	267.00	D953515	1.00	<0.005		0.001
			267.00	268.50	D953516	1.50	<0.005		0.001
			268.50	270.00	D953517	1.50	<0.005		0.001
			270.00	271.50	D953518	1.50	0.005		0.005
			271.50	273.00	D953519	1.50	0.005		0.005
			273.00	274.50	D953521	1.50	<0.005		0.001
			274.50	276.00	D953522	1.50	<0.005		0.001
			276.00	277.50	D953523	1.50	0.005		0.005
			277.50	279.00	D953524	1.50	<0.005		0.001
			279.00	280.50	D953525	1.50	<0.005		0.001
			280.50	282.00	D953526	1.50	<0.005		0.001
			282.00	283.50	D953527	1.50	0.005		0.005
			283.50	285.20	D953528	1.70	0.005		0.005
			285.20	286.70	79862	1.50	<0.005		0.001
			286.70	287.00	79869	0.30	<0.005		0.001
			287.00	288.00	79863	1.00	<0.005		0.001
			288.00	289.50	D953529	1.50	0.036		0.036
			289.50	291.00	D953531	1.50	0.005		0.005
			291.00	292.50	D953532	1.50	<0.005		0.001
			292.50	294.00	D953533	1.50	0.005		0.005
			294.00	295.50	D953534	1.50	0.005		0.005
			295.50	297.00	D953535	1.50	<0.005		0.001
			297.00	298.50	D953536	1.50	0.007		0.007
			298.50	300.00	D953537	1.50	<0.005		0.001
			300.00	301.50	D953538	1.50	<0.005		0.001
			301.50	303.00	D953539	1.50	0.005		0.005
			303.00	304.50	D953541	1.50	0.005		0.005
304.50	306.00	D953542	1.50	0.010		0.010			
306.00	307.50	D953543	1.50	<0.005		0.001			
307.50	309.00	D953544	1.50	<0.005		0.001			
309.00	310.50	D953546	1.50	0.006		0.006			
310.50	312.00	D953547	1.50	<0.005		0.001			
312.00	313.00	D953548	1.00	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			313.00	314.00	D953549	1.00	<0.005		0.001
			314.00	315.00	79864	1.00	<0.005		0.001
			315.00	316.00	79865	1.00	<0.005		0.001
			316.00	317.00	79866	1.00	<0.005		0.001
			317.00	318.00	D953551	1.00	0.005		0.005
			318.00	319.50	D953552	1.50	0.005		0.005
			319.50	321.00	D953553	1.50	<0.005		0.001
			321.00	322.50	D953554	1.50	0.005		0.005
			322.50	324.00	D953555	1.50	0.012		0.012
			324.00	325.50	D953556	1.50	<0.005		0.001
			325.50	327.00	D953557	1.50	0.010		0.010
326.70	327.20	B1ch <b>Bleaching</b> light green, +/- bleached, 1-2% cm-cubic Py	327.00	328.50	D953558	1.50	<0.005		0.001
			328.50	330.00	D953559	1.50	0.005		0.005
			330.00	331.50	D953561	1.50	<0.005		0.001
			331.50	333.00	D953562	1.50	<0.005		0.001
			333.00	334.50	D953563	1.50	<0.005		0.001
			334.50	336.10	D953564	1.60	0.005		0.005
336.00	338.60	BX <b>Breccia</b> 70-75% Qtz-Carb injected to loc. hydro-brecciated, loc. +/- seric	336.10	337.60	79867	1.50	<0.005		0.001
			337.60	338.60	79868	1.00	<0.005		0.001
338.60	Fin du sondage								
	Nombre d'échantillons : 220								
	Nombre d'échantillons QAQC : 26								
	Longueur totale échantillonnée : 295.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
58.50	58.50	D953370	O54Pa	0.00	3.140	3.140
72.00	73.50	D953380	D953379	1.50	<0.005	0.001
78.00	78.00	D953385	m	0.00	<0.005	0.001
84.00	84.00	D953390	O53Pb	0.00	0.764	0.764
97.80	99.00	D953400	D953399	1.20	<0.005	0.001
111.00	111.00	D953410	O54Pa	0.00	3.140	3.140
125.40	127.00	D953420	D953419	1.60	<0.005	0.001
133.90	133.90	79840	O53Pb	0.00	0.617	0.617
133.90	133.90	79841	m	0.00	<0.005	0.001
138.00	138.00	D953430	O52Pb	0.00	0.334	0.334
156.00	157.00	D953440	D953439	1.00	<0.005	0.001
162.00	162.00	D953445	m	0.00	<0.005	0.001
168.00	168.00	D953450	O53Pb	0.00	0.742	0.742
189.00	190.50	D953460	D953459	1.50	<0.005	0.001
219.00	220.00	D953480	D953479	1.00	<0.005	0.001
225.00	225.00	D953485	m	0.00	<0.005	0.001
231.00	231.00	D953490	O52Pb	0.00	0.291	0.291
244.00	245.20	D953500	D953499	1.20	0.006	0.006
246.20	246.20	79860	O53Pb	0.00	0.665	0.665
258.00	258.00	D953510	O53Pb	0.00	0.601	0.601
271.50	273.00	D953520	D953519	1.50	0.005	0.005
288.00	288.00	D953530	O54Pa	0.00	2.950	2.950
301.50	303.00	D953540	D953539	1.50	<0.005	0.001
307.50	307.50	D953545	m	0.00	<0.005	0.001
313.00	313.00	D953550	O52Pb	0.00	0.314	0.314
328.50	330.00	D953560	D953559	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-66	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multi Drill	Lot :	
Décrit par : Geneviève Carignan	Du : 2009-06-21	Date de description : 2009-06-24
	Au : 2009-07-07	

Collet

Azimut : 313.97°		UTM
Plongée : -47.50°		Est 630 829.8
Longueur : 200.00 m		Nord 5 374 362.2
		Élévation 309.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide		Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	347.45°	-46.70°	Non						
Reflex	60.00	345.50°	-45.10°	Non						
Reflex	123.00	347.20°	-43.10°	Non						
Reflex	150.00	348.80°	-42.20°	Non						
Reflex	180.00	345.60°	-40.70°	Non						

Description

GPS Datum NAD83, UTM Zone 17.

Dimension de la carotte : NQ	Cimenté : Non	Entreposé : Oui
------------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.10	MT <b>Casing</b> Casing 2.1m							
2.10	20.55	SY PT POR <b>Syenite Lath Porphyry Intrusive</b> Syenite Lath intrusive. Light purple to purple-green. Fld lath highly chloritised and epidotized.. Small white halo around Fld (albitisation). Laths are 2-3mm X 7-10mm. Around 30% laths. 5% euhedrals phenos (3-10mm). Micro-fractures filled by chlorite. Silica-carbonate flooding. <1% quartz vein.  Overall alterations: medium CHL, medium EPI, medium SIL, weak CARB and medium ALB. Pervasive meteoric water alteration. Low mag.  Trace to no mineralization. Foliation 40 TCA.  10.8m-20.05m : Fld completely altered (<5% visible). Strong CHL, SIL and EPI alterations. Weak pervasive fuschite. 10-15% micro-fractured (tension) filled by chlorite. 1-3% Py. Sharp lower contact 40 TCA.	2.10	3.00	P003430	0.90	0.051		0.051
			3.00	4.50	P003431	1.50	0.208		0.208
4.00	10.50	FRC; BC <b>Fractured 40°; Broken Core</b> Fractured and broken core (20%)	4.50	6.00	P003432	1.50	0.266		0.266
			6.00	7.50	P003433	1.50	0.251		0.251
			7.50	9.00	P003434	1.50	0.251		0.251
			9.00	10.50	P003435	1.50	0.104		0.104
			10.50	12.00	P003436	1.50	0.048		0.048
10.80	20.50	Chl60; Epi60; FCT10; Sil50 <b>Chloritisation 60; Epidotisation 60; Fuchsitization 10; Silicification 50</b> strong alterations	12.00	13.50	P003437	1.50	0.019		0.019
			13.50	15.00	P003438	1.50	0.076		0.076
			15.00	16.50	P003439	1.50	0.141		0.141
			16.50	18.00	P003440	1.50	0.085		0.085
17.80	17.84	VEI;4;Qz;T;30°;; <b>Vein 4 Quartz Tension 30°</b> qtz vein	18.00	19.50	P003441	1.50	0.028		0.028
			19.50	21.00	P003442	1.50	0.277		0.277
20.55	34.60	BSF <b>Breccia silicified zone</b> Breccia. Gray to dark gray green. Strong silicification and chloritisation, weak epidotisation.Pervasive bleaching. Interdigitation with I2D at upper contact. Small stockworks silica veinlets intervals. 25% fld phenos <10mm, chloritised and albitised.							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
20.55	34.60	<p>Matrix is silica. 40-60% smokey quartz. 5-30% disseminated Py and stringers. Sharp upper contact 40 TCA and lower contact 80 TCA.</p> <p>Py05; Py30</p> <p><b>Pyrite 05%; Pyrite 30%</b></p> <p>5-30% disseminated Py and stringers</p>	21.00	22.50	P003443	1.50	0.847		0.847
			22.50	24.00	P003445	1.50	0.994		0.994
			24.00	25.50	P003446	1.50	1.365		1.365
			25.50	27.00	P003447	1.50	4.370	4.34	4.340
			27.00	28.50	P003448	1.50	7.030	6.66	6.660
			28.50	30.00	P003449	1.50	7.820	7.53	7.530
			30.00	31.50	P003450	1.50	6.360	8.20	8.200
			31.50	33.00	P003451	1.50	2.190		2.190
			33.00	34.50	P003452	1.50	4.030	5.17	5.170
			34.50	36.00	P003453	1.50	0.009		0.009
34.60	200.00	<p>SY POR</p> <p><b>Syenite Porphyry Intrusive</b></p> <p>Red to dark-red-green. Fine to medium grains. 20% euhedrals Fld phenos (2-6mm) moderately albitized and epidotized. Mag +++ . 10% micro-fractures filled by silica-carbonate fluids and chlorite. Foliation 40 TCA. Small breccia intervals &lt;10cm, matrix silica. Tr hematite (mostly in Qz veins).</p> <p>Overall groundmass alteration is medium Chlorite, medium epidote, weak albite. weak to medium silica and weak potassic. Strong pervasive epidote alteration within foliation.</p> <p>Locally anastomosing veinlets of Chlorite &gt;1mm.</p> <p>Trace to 2-3% Py. Tr Cp(in a Qz vein). Less than 1% quartz veins, locally 5-10%.</p>	36.00	37.50	P003454	1.50	0.008		0.008
			37.50	39.00	P003455	1.50	<0.005		0.001
			39.00	40.50	P003456	1.50	<0.005		0.001
			40.50	42.00	P003457	1.50	0.027		0.027
			42.00	43.50	P003458	1.50	<0.005		0.001
			43.50	45.00	P003459	1.50	<0.005		0.001
			45.00	46.50	P003460	1.50	0.007		0.007
			46.50	48.00	P003461	1.50	0.086		0.086
			48.00	49.50	P003462	1.50	0.006		0.006
49.20	60.20	<p>Chl60; Epi60; Sil40; Alb30</p> <p><b>Chloritisation 60; Epidotisation 60; Silicification 40;</b></p> <p><b>Albitisation 30</b></p> <p>strong alterations</p>	49.50	51.00	P003463	1.50	0.011		0.011
			51.00	52.50	P003465	1.50	0.007		0.007
			52.50	54.00	P003466	1.50	0.182		0.182
			54.00	55.50	P003467	1.50	0.043		0.043
			55.50	57.00	P003468	1.50	0.018		0.018
			57.00	58.50	P003469	1.50	0.148		0.148
			58.50	60.00	P003470	1.50	0.632		0.632

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			60.00	61.50	P003471	1.50		0.053		0.053
			61.50	62.90	P003472	1.40		0.006		0.006
			62.90	64.50	P003473	1.60		0.132		0.132
			64.50	66.00	P003474	1.50		0.019		0.019
			66.00	67.50	P003475	1.50		0.017		0.017
			67.50	69.00	P003476	1.50		0.042		0.042
			69.00	70.50	P003477	1.50		0.020		0.020
			70.50	72.00	P003478	1.50		0.080		0.080
			72.00	73.50	P003479	1.50		0.412		0.412
73.20	73.50	Py	73.50	75.00	P003480	1.50		0.068		0.068
		<b>Pyrite</b>	75.00	76.50	P003481	1.50		0.060		0.060
		4-6% very fine to fine disseminated pyrite.	76.50	78.00	P003482	1.50		0.666		0.666
76.60	82.20	Epi; Chl	78.00	79.50	P003483	1.50		0.141		0.141
		<b>Epidotisation; Chloritisation</b>	79.50	81.00	P003484	1.50		0.021		0.021
		Moderate pervasive epidotisation with light to moderate chloritisation in fine dark green stringers and around phenos.	81.00	82.50	P003485	1.50		0.257		0.257
			82.50	84.00	P003486	1.50		0.024		0.024
		1-2% fine to loc medium disseminated pyrite (loc cubic).	84.00	85.50	P003488	1.50		0.112		0.112
85.20	87.00	Car	85.50	87.00	P003489	1.50		0.068		0.068
		<b>Carbonatisation</b>	87.00	88.50	P003490	1.50		<0.005		0.001
		Light carbonatisation as injections.	88.50	90.00	P003491	1.50		0.008		0.008
			90.00	91.50	P003492	1.50		<0.005		0.001
			91.50	93.00	P003493	1.50		0.081		0.081
			93.00	94.50	P003494	1.50		<0.005		0.001
			94.50	96.00	P003495	1.50		0.013		0.013
			96.00	97.50	P003496	1.50		0.083		0.083
			97.50	99.00	P003497	1.50		<0.005		0.001
			99.00	100.50	P003498	1.50		<0.005		0.001
			100.50	102.00	P003499	1.50		<0.005		0.001
			102.00	103.50	P003500	1.50		<0.005		0.001
			103.50	105.00	P003501	1.50		<0.005		0.001
			105.00	106.50	P003502	1.50		0.035		0.035
106.15	108.80	Epi; Chl; Ser	106.50	108.00	P003503	1.50		0.035		0.035
		<b>Epidotisation; Chloritisation; Sericitisation</b>	108.00	109.50	P003504	1.50		0.014		0.014
		Epi pervasive, Ser pervasive and chloritisation along foliation.								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			109.50	111.00	P003505	1.50	0.005		0.005
			111.00	112.50	P003506	1.50	0.027		0.027
			112.50	114.00	P003507	1.50	<0.005		0.001
			114.00	115.50	P003508	1.50	0.005		0.005
			115.50	117.00	228910	1.50	0.049		0.049
116.70	119.40	Epi; Ser <b>Epidotisation; Sericitisation</b> Epi pervasive, Ser along along foliation.							
116.70	119.40	Py03 <b>Pyrite 03%</b> 2-3% fine disseminated (mostly cubic).	117.00	118.50	228911	1.50	0.646		0.646
			118.50	119.60	228912	1.10	0.360		0.360
			119.60	120.50	206828	0.90	0.365		0.365
			120.50	122.00	206829	1.50	<0.005		0.001
			122.00	123.50	206830	1.50	<0.005		0.001
122.80	124.40	Chl; Ser <b>Chloritisation; Sericitisation</b> Moderate chloritisation and sericitisation making foliation @ 50-60° TCA.	123.50	125.00	206831	1.50	0.030		0.030
			125.00	126.50	206832	1.50	0.022		0.022
125.20	126.40	Chl; Ser <b>Chloritisation; Sericitisation</b> Moderate chloritisation and sericitisation making foliation @ 50-60° TCA.	126.50	128.00	206833	1.50	0.088		0.088
			128.00	129.50	206834	1.50	<0.005		0.001
			129.50	131.00	206836	1.50	<0.005		0.001
			131.00	132.50	206837	1.50	<0.005		0.001
			132.50	134.00	206838	1.50	<0.005		0.001
			134.00	135.50	206839	1.50	0.203		0.203
			135.50	137.00	206840	1.50	<0.005		0.001
			137.00	138.50	206841	1.50	<0.005		0.001
			138.50	140.00	206842	1.50	<0.005		0.001
			140.00	141.50	206843	1.50	0.006		0.006
140.70	145.90	Chl; Ser; Epi <b>Chloritisation; Sericitisation; Epidotisation</b> Moderate sericitisation with light chloritisation and epidotisation.	141.50	143.00	206844	1.50	0.006		0.006
			143.00	144.50	206845	1.50	0.068		0.068
			144.50	146.00	206846	1.50	0.059		0.059
			146.00	147.50	206847	1.50	0.063		0.063
			147.50	149.00	206848	1.50	0.105		0.105
			149.00	150.50	206849	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
150.60	159.50	Ser; Epi; Chl <b>Sericitisation; Epidotisation; Chloritisation</b> Moderate sericitisation with light epidotisation and chloritisation making a foliation @ 20-40° TCA. 2-3% white Qz veins and injections.	150.50	152.00	206850	1.50	0.057		0.057
			152.00	153.50	206851	1.50	<0.005		0.001
			153.50	155.00	206852	1.50	<0.005		0.001
			155.00	156.50	206853	1.50	<0.005		0.001
			156.50	158.00	206854	1.50	<0.005		0.001
			158.00	159.50	206856	1.50	0.010		0.010
			159.50	161.00	206857	1.50	<0.005		0.001
			161.00	162.50	206858	1.50	<0.005		0.001
			162.50	164.00	206859	1.50	<0.005		0.001
			164.00	165.50	206860	1.50	<0.005		0.001
			165.50	167.00	206861	1.50	<0.005		0.001
166.80	185.40	Ser; Chl <b>Sericitisation; Chloritisation</b> Moderate to high sericitisation and chloritisation. High foliation @ 40-50° TCA with 3% white Qz veins @ 40-50° TCA and injections.	167.00	168.50	206862	1.50	<0.005		0.001
			168.50	170.00	206863	1.50	<0.005		0.001
			170.00	171.50	206864	1.50	0.053		0.053
			171.50	173.00	206865	1.50	0.097		0.097
			173.00	174.50	206866	1.50	0.005		0.005
			174.50	176.00	206867	1.50	<0.005		0.001
			176.00	177.50	206868	1.50	<0.005		0.001
			177.50	179.00	206869	1.50	<0.005		0.001
			179.00	180.50	206870	1.50	<0.005		0.001
			180.50	182.00	206871	1.50	0.005		0.005
			182.00	183.50	206872	1.50	<0.005		0.001
183.50	185.00	206873	1.50	<0.005		0.001			
185.00	186.50	206874	1.50	0.919		0.919			
185.40	186.40	Sil; Car <b>Silicification; Carbonatisation</b> Moderate pervasive grey silicification and light to moderate carbonatisation as injections.  Sharp contacts @ 45° TCA.							
185.40	186.40	Py03 <b>Pyrite 03%</b> 2-3% very fine disseminated pyrite.							
186.40	193.00	Chl <b>Chloritisation</b>	186.50	188.00	206876	1.50	0.036		0.036
			188.00	189.50	206877	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Moderate chloritisation along foliation and pervasive in matrix.	189.50	191.00	206878	1.50	0.059		0.059
	191.00	192.50	206879	1.50	0.269		0.269
	192.50	194.00	206880	1.50	0.102		0.102
	194.00	195.50	206881	1.50	<0.005		0.001
	195.50	197.00	206882	1.50	<0.005		0.001
	197.00	198.50	206883	1.50	0.138		0.138
	198.50	200.00	206884	1.50	0.028		0.028
200.00	Fin du sondage Nombre d'échantillons : 133 Nombre d'échantillons QAQC : 6 Longueur totale échantillonnée : 197.90						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
21.00	22.50	P003444	O53Pb	1.50	0.617	0.617
49.50	51.00	P003464	O54Pa	1.50	2.700	2.700
82.50	84.00	P003487	O52Pb	1.50	0.330	0.330
128.00	128.00	206835	O61d	0.00	4.810	5.080
156.50	156.50	206855	O7Pb	0.00	2.750	2.750
185.00	185.00	206875	O15Pa	0.00	0.995	0.995

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-67	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multi Drill	Lot :	
Décrit par : Dominic Fleming	Du : 2009-07-07	Date de description : 2009-07-10
	Au : 2009-07-10	

Collet

Azimut : 348.37°		UTM
Plongée : -45.70°		Est 630 964.1
Longueur : 200.00 m		Nord 5 374 377.8
		Élévation 313.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide		Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	2.80°	-44.70°	Non						
Reflex	60.00	2.10°	-43.70°	Non						
Reflex	90.00	3.50°	-42.40°	Non						
Reflex	120.00	5.30°	-41.30°	Non						
Reflex	150.00	5.30°	-40.60°	Non						
Reflex	180.00	5.30°	-39.00°	Non						

Description

GPS Datum NAD83 Zone17

Re-sampled by: V. Nadeau Benoit (02/06/2010)

Dimension de la carotte : NQ	Cimenté : Non	Entreposé : Oui
------------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.80	MT <b>Casing</b> Casing 3.8m							
3.80	200.00	SY POR <b>Syenite Porphyry Intrusive</b> Red to red-green-dark gray. Fine grains. 10-20% euhedrals phenos (<10mm). Fld are medium albitised (halo around fld) and weak chloritised+epidotized. 5-10% extension fractures filled by silica-carbonate fluids <5mm @30-60 TCA, mostly albitized. Locally up to 40% (18m-22m) (anastomose). Higher intensity in altered intervals (EPI-CHL-ALB). Tecto-brecciated.  1-2% micro-fractures filled by sericite and chlorite+magnetite.  Overall groundmass alterations: Medium Albite, weak CARB, weak sericite, weak silica, medium epidote and medium chlorite. Pervasive strong sericite and epidote. Locally weak fuschite. Strong wheathering from 7.8m to 16.8m and core 80% fractured.  Trace to 2-3% disseminated Py and cubic Py. Low mag to strong mag. 140m-200m (mag+++).  75.0m-79.7m and 127m-129.9m: Intense fractures filled by CHL+SER.  147.8m-154.6m : 75% milky white veins, Intense albitization.Foliation 50 TCA.  VNB (02/06/2010): 154.50 m - 158.50: Syenite with lath porphyry feldspar. Phenos are up to 2 cm long and about 10-15% of the rock. rock is altered and the contact between this sub-unit and the rest appear to be not really sharp compared to what we usually see with the Lath Porphyry Syenite.  179.5m-200m : <5% Fld phenos (monzonite)  E.O.H. : 200m	3.80	4.50	P002062	0.70	0.012		0.012
			4.50	6.00	P002063	1.50	0.042		0.042
6.00	6.70	Epi60; Ser30 <b>Epidotisation 60; Sericitisation 30</b> strong alterations	6.00	7.50	P002064	1.50	<0.005		0.001
			7.50	9.00	P002065	1.50	0.007		0.007



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
7.80	16.80	Wea90 <b>Weathering (Incl. Saprolitic alter.) 90</b> strong wheathering						
7.80	16.80	BC; FRC <b>Broken Core ; Fractured</b> 80% broken core	9.00	10.50	P002066	1.50	0.064	0.064
			10.50	12.00	P002067	1.50	0.039	0.039
			12.00	13.50	P002068	1.50	0.020	0.020
			13.50	15.00	P002069	1.50	0.209	0.209
			15.00	16.50	P002070	1.50	0.855	0.855
			16.50	18.00	P002071	1.50	0.040	0.040
			18.00	19.50	P002072	1.50	0.045	0.045
			19.50	21.00	P002073	1.50	0.151	0.151
			21.00	22.50	P002074	1.50	1.915	1.915
22.50	39.30	Py02; Py15 <b>Pyrite 02%; Pyrite 15%</b> 2-10% fine disseminated Py	22.50	24.00	P002075	1.50	0.406	0.406
23.80	27.30	Epi40 <b>Epidotisation 40</b> medium epidote	24.00	25.50	P002076	1.50	0.189	0.189
			25.50	27.00	P002077	1.50	0.095	0.095
			27.00	28.50	P002078	1.50	1.085	1.085
28.00	39.30	BSF <b>Breccia silicified zone</b> Breccia. Gradational upper and lower contact. Matrix silica. 30-40% phenos (fld+syenite). Albite halo around phenos, epidotised. Foliation 40 TCA. Strong silica alteration, moderate epidote alteration and chlorite alteration. Strong epidote alteration at upper (23.8m-27.3m) and lower contact (34m-39m). Locally bleaching and albitization. Wheathering from 31.5m to 33.5m.  5-10 tensions veins <3mm filled by silica.  2-15% fine disseminated Py.						
28.00	39.30	FOL <b>Foliation 40°</b> fol 40	28.50	30.00	P002079	1.50	0.761	0.761
			30.00	31.50	P002081	1.50	3.060	3.13
31.50	33.50	Wea70 <b>Weathering (Incl. Saprolitic alter.) 70</b> wheathering	31.50	33.00	P002082	1.50	4.040	4.13
			33.00	34.50	P002083	1.50	2.130	2.130
34.00	39.00	Epi60; Blch20; Alb10	34.50	36.00	P002084	1.50	1.345	1.345

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
		<b>Epidotisation 60; Bleaching 20; Albitisation 10</b> strong alterations	36.00	37.50	P002085	1.50	0.272		0.272			
			37.50	39.00	P002086	1.50	0.326		0.326			
			39.00	40.50	P002087	1.50	0.061		0.061			
			40.50	42.00	P002088	1.50	0.055		0.055			
			42.00	43.50	P002089	1.50	0.113		0.113			
42.40	43.90	Epi50; Ser30 <b>Epidotisation 50; Sericitisation 30</b> strong alterations										
43.20	43.24	VEI;4;Sq;T;60°;; <b>Vein 4 Smokey Quartz Tension 60°</b> qtz vein	43.50	45.00	P002090	1.50	0.051		0.051			
			45.00	46.50	P002091	1.50	0.100		0.100			
46.00	50.60	Epi70; Chl30; FCT20 <b>Epidotisation 70; Chloritisation 30; Fuchsitization 20</b> strong alterations										
			46.10	46.13	VEI;3;SqAb;T;50°;Hm02; <b>Vein 3 Smokey Quartz Albite Tension 50° Hematite02</b> qtz-alb vein	46.50	48.00	P002092	1.50	0.005		0.005
			48.00	49.50	P002093	1.50	0.079		0.079			
49.50	67.50	Py02; Py20 <b>Pyrite 02%; Pyrite 20%</b> 2-20% fine disseminated Py	49.50	51.00	P002094	1.50	0.558		0.558			
50.60	67.70	BSF <b>Breccia silicified zone</b> same as 28m-39.3m.	51.00	52.50	P002095	1.50	0.386		0.386			
			52.50	54.00	P002096	1.50	0.934		0.934			
			54.00	55.50	P002097	1.50	1.415		1.415			
		Sericitisation in foliation. Fol 70 TCA.										
		Upper contact sharp 60 TCA.										
		2-20% fine disseminated Py										
54.50	54.60	VEI;10;AbQzCc;;70°;; <b>Vein 10 Albite Quartz Calcite 70°</b> qtz-alb-calc vein	55.50	57.00	P002099	1.50	0.672		0.672			
			57.00	58.50	P002100	1.50	0.295		0.295			
			58.50	60.00	P002101	1.50	0.363		0.363			
			60.00	61.50	P002102	1.50	0.938		0.938			
			61.50	63.00	P002103	1.50	2.420		2.420			
			63.00	64.50	P002104	1.50	1.100		1.100			

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			64.50	66.00	P002105	1.50		0.028		0.028
			66.00	67.50	P002106	1.50		0.550		0.550
			67.50	69.00	P002107	1.50		0.007		0.007
			69.00	70.50	P002108	1.50		0.058		0.058
70.00	79.00	FOL <b>Foliation 40°</b> fol 40	70.50	72.00	P002109	1.50		0.183		0.183
			72.00	73.50	P002110	1.50		0.032		0.032
			73.50	75.00	P002111	1.50		0.248		0.248
75.00	79.70	Chl50; Epi20; Ser30 <b>Chloritisation 50; Epidotisation 20; Sericitisation 30</b> Strong alterations	75.00	76.50	203551	1.50		0.050		0.050
			76.50	78.00	203552	1.50		0.024		0.024
			78.00	79.50	203553	1.50		0.230		0.230
			79.50	81.00	203554	1.50		0.006		0.006
			81.00	82.50	203555	1.50		<0.005		0.001
			82.50	84.00	203556	1.50		0.005		0.005
			84.00	85.50	203557	1.50		0.006		0.006
			85.50	87.00	203558	1.50		0.084		0.084
87.00	93.60	Epi60; Chl40; Ser20; Alb20 <b>Epidotisation 60; Chloritisation 40; Sericitisation 20;</b> <b>Albitisation 20</b> strong alterations	87.00	88.50	203559	1.50		<0.005		0.001
			88.50	90.00	203560	1.50		0.006		0.006
			90.00	91.50	203562	1.50		0.059		0.059
			91.50	93.00	203563	1.50		0.089		0.089
			93.00	94.50	203564	1.50		<0.005		0.001
			94.50	96.00	203565	1.50		<0.005		0.001
95.60	99.10	Chl50; Ser30 <b>Chloritisation 50; Sericitisation 30</b> strong alterations	96.00	97.50	203566	1.50		<0.005		0.001
			97.50	99.00	203567	1.50		<0.005		0.001
			99.00	100.50	203568	1.50		<0.005		0.001
			100.50	102.00	203569	1.50		0.007		0.007
101.00	125.00	FOL <b>Foliation 35°</b> fol 35 TCA								
101.60	103.20	Chl60; Ser40; Epi20 <b>Chloritisation 60; Sericitisation 40; Epidotisation 20</b> strong alterations	102.00	103.50	203570	1.50		0.024		0.024
102.50	102.52	VE1;2;Qz;T;70°;Cp005; <b>Vein 2 Quartz Tension 70° Chalcopyrite005%</b> qtz vein with 0.5% Cp0								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
103.10	103.12	VEI;2;CcQz;T;60°;; <b>Vein 2 Calcite Quartz Tension 60°</b> qtz-calcite vein	103.50	105.00	203571	1.50	<0.005		0.001
			105.00	106.50	203572	1.50	<0.005		0.001
105.25	107.00	Pot70; Chl25; Epi20 <b>Potassic alteration 70; Chloritisation 25; Epidotisation 20</b> strong alterations	106.50	108.00	203573	1.50	<0.005		0.001
			108.00	109.50	D915212	1.50	<0.005		0.001
			109.50	111.00	D915213	1.50	<0.005		0.001
			111.00	112.00	D915214	1.00	<0.005		0.001
			112.00	113.00	D915215	1.00	0.005		0.005
			113.00	114.50	203574	1.50	<0.005		0.001
			114.50	116.00	203575	1.50	<0.005		0.001
114.85	114.95	VEI;10;AbQz;T;;Py02Hm03; <b>Vein 10 Albite Quartz Tension Pyrite02% Hematite03%</b> qtz-alb vein 2%Py-3%Hem	116.00	117.50	203576	1.50	0.068		0.068
			117.50	119.00	203577	1.50	0.006		0.006
			119.00	120.00	D915216	1.00	0.005		0.005
			120.00	121.50	D915217	1.50	0.005		0.005
			121.50	123.00	D915218	1.50	0.005		0.005
			123.00	124.50	D915219	1.50	0.005		0.005
			124.50	125.90	D915221	1.40	0.005		0.005
			125.90	126.90	203578	1.00	0.005		0.005
127.00	129.90	Chl60; Ser30; Epi10 <b>Chloritisation 60; Sericitisation 30; Epidotisation 10</b> strong alterations	126.90	127.90	203579	1.00	0.008		0.008
			127.90	128.90	203580	1.00	0.006		0.006
			128.90	129.90	203582	1.00	0.006		0.006
			129.90	130.90	203583	1.00	0.006		0.006
			130.90	131.90	203584	1.00	0.034		0.034
			131.90	133.50	D915222	1.60	<0.005		0.001
			133.50	135.00	D915223	1.50	0.005		0.005
			135.00	136.50	D915224	1.50	0.006		0.006
139.45	143.90	Epi50; Chl30; Ser20 <b>Epidotisation 50; Chloritisation 30; Sericitisation 20</b> strong alterations	136.50	138.00	D915225	1.50	0.005		0.005
			138.00	139.45	D915226	1.45	0.008		0.008
			139.45	141.00	D915227	1.55	<0.005		0.001
			141.00	142.50	D915228	1.50	0.036		0.036
			142.50	143.90	D915229	1.40	0.028		0.028
			143.90	145.50	D915231	1.60	0.012		0.012
			145.50	147.00	D915232	1.50	0.024		0.024

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
147.80	154.60	Epi60; Ch140; Alb70; Ser25 <b>Epidotisation 60; Chloritisation 40; Albitisation 70;</b> <b>Sericitisation 25</b> strong alterations	147.00	148.00	203585	1.00	0.006		0.006
			148.00	149.50	203586	1.50	0.005		0.005
			149.50	151.00	203587	1.50	0.207		0.207
			151.00	152.50	203588	1.50	0.590		0.590
			152.50	154.00	203589	1.50	0.027		0.027
			154.00	155.50	203590	1.50	0.039		0.039
155.00	159.00	BC; FRC <b>Broken Core ; Fractured</b> broken core	155.50	157.00	203591	1.50	0.651		0.651
			157.00	158.50	203592	1.50	0.193		0.193
			158.50	160.00	D915233	1.50	<0.005		0.001
			160.00	161.00	D915234	1.00	0.093		0.093
			161.00	162.00	D915235	1.00	0.895		0.895
			162.00	163.50	D915236	1.50	0.009		0.009
			163.50	165.00	D915237	1.50	0.009		0.009
			165.00	166.50	D915238	1.50	0.011		0.011
		166.50	168.00	D915239	1.50	0.017		0.017	
166.80	166.83	VEI;3;Cc;T;60°;; <b>Vein 3 Calcite Tension 60°</b> calcite vein							
167.25	167.28	VEI;3;CcQz;T;70°;Hm05; <b>Vein 3 Calcite Quartz Tension 70° Hematite05%</b> qtz-calcite vein 5%hem	168.00	169.50	D915241	1.50	0.005		0.005
			169.50	170.90	D915242	1.40	0.008		0.008
170.00	200.00	FOL <b>Foliation 60°</b> fol. 60 TCA							
170.87	171.20	VEI;25;Cc;T;45°;; <b>Vein 25 Calcite Tension 45°</b> Added by VNB (2010/06/02): 25cm thick white-pinkish calcite vein. barren	170.90	172.50	D915243	1.60	<0.005		0.001
			172.50	174.00	D915244	1.50	0.024		0.024
			174.00	175.50	D915246	1.50	0.029		0.029
			175.50	177.00	D915247	1.50	0.006		0.006
			177.00	178.50	D915248	1.50	0.007		0.007
			178.50	180.00	D915249	1.50	<0.005		0.001
			180.00	181.50	203593	1.50	0.013		0.013
			181.50	183.00	203594	1.50	0.005		0.005
		183.00	184.50	203595	1.50	<0.005		0.001	
		184.50	186.00	D915251	1.50	0.005		0.005	

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			186.00	187.50	D915252	1.50		0.512		0.512
			187.50	189.00	D915253	1.50		0.055		0.055
			189.00	190.50	D915254	1.50		0.005		0.005
			190.50	192.00	D915255	1.50		<0.005		0.001
			192.00	193.05	D915256	1.05		<0.005		0.001
193.00	194.50	Chl50; Epi40; Sil20; Ser20	193.05	194.40	D915257	1.35		0.222		0.222
		<b>Chloritisation 50; Epidotisation 40; Silicification 20;</b>	194.40	195.90	D915258	1.50		0.165		0.165
		<b>Sericitisation 20</b>								
		strong alterations								
194.50	200.00	Pot20	195.90	197.00	D915259	1.10		0.007		0.007
		<b>Potassic alteration 20</b>	197.00	198.50	203596	1.50		0.007		0.007
		pot. alt	198.50	200.00	203597	1.50		<0.005		0.001
200.00	Fin du sondage									
	Nombre d'échantillons : 136									
	Nombre d'échantillons QAQC : 11									
	Longueur totale échantillonnée : 196.20									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
28.50	28.50	P002080	O54Pa	0.00	2.860	2.860
54.00	54.00	P002098	O53Pb	0.00	0.615	0.615
60.00	61.50	203541	O7Pb	1.50	2.890	3.010
88.50	90.00	203561	O15Pa	1.50	0.989	0.989
123.00	124.50	D915220	D915219	1.50	<0.005	0.001
127.90	128.90	203581	O53Pb	1.00	0.619	0.619
142.50	142.50	D915230	O53Pb	0.00	0.648	0.648
166.50	168.00	D915240	D915239	1.50	<0.005	0.001
172.50	172.50	D915245	m	0.00	<0.005	0.001
178.50	178.50	D915250	O54Pa	0.00	2.890	2.890
195.90	197.00	D915260	D915259	1.10	0.013	0.013

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-68	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : MultiDrill	Lot :	
Décrit par : H.Tazerout	Du : 2009-07-10	Date de description : 2009-07-12
	Au : 2009-07-12	

Collet

Azimut : 136.56°  
 Plongée : -65.00°  
 Longueur : 200.00 m

UTM

Est	630 021.6
Nord	5 374 530.9
Élévation	280.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	136.56°	-65.31°	Non
Reflex	5.00	136.90°	-64.89°	Non
Reflex	10.00	137.84°	-64.78°	Non
Reflex	15.00	138.44°	-65.23°	Non
Reflex	20.00	138.64°	-65.56°	Non
Reflex	25.00	138.93°	-65.54°	Non
Reflex	30.00	138.90°	-65.57°	Non
Reflex	35.00	139.09°	-65.43°	Non
Reflex	40.00	139.52°	-65.21°	Non
Reflex	45.00	139.75°	-65.08°	Non
Reflex	50.00	139.83°	-64.86°	Non
Reflex	55.00	139.95°	-64.68°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	60.00	139.98°	-64.44°	Non
Reflex	65.00	140.36°	-64.18°	Non
Reflex	70.00	140.50°	-63.98°	Non
Reflex	75.00	140.76°	-63.79°	Non
Reflex	80.00	140.83°	-63.66°	Non
Reflex	85.00	140.88°	-63.47°	Non
Reflex	90.00	141.03°	-63.26°	Non
Reflex	95.00	141.02°	-63.12°	Non
Reflex	100.00	141.05°	-62.97°	Non
Reflex	105.00	140.91°	-62.75°	Non
Reflex	110.00	140.91°	-62.54°	Non
Reflex	115.00	141.06°	-62.38°	Non

Description

NAD 83, UTM Zone 17

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	34.20	MT <b>Casing</b> CASING							
34.20	139.95	BA; FOL <b>Mafic Meta-Volcanic ; Foliation</b> Green to dark green, medium grain to loc coarse grain, highly foliated@25-45°TCA & loc highly foliated@0-10°TCA. Moderatly fractured & filled with a white Alb+ /+++ Qtz-Carb fluid or by a dark Chl. 2-3% white Alb+ /+++ Vl & V Qtz-Carb@20-50°TCA<7.0cm. 5-7% white Alb+++ Qtz-Carb specks<0.3cm. Loc buff-yellow to greenish Ser++ along fractures & foliation. Carb++ to loc Carb+++. Tr fine diss Py. Lower Contact@10°TCA.  **locally brecciated with silica flooding.	34.20	35.00	D911387	0.80	<0.005		0.001
			35.00	36.50	D911388	1.50	0.005		0.005
			36.50	38.00	D911389	1.50	<0.005		0.001
			38.00	39.50	D911391	1.50	<0.005		0.001
			39.50	41.00	D911392	1.50	0.005		0.005
			41.00	42.50	D911393	1.50	<0.005		0.001
			42.50	44.00	D911394	1.50	<0.005		0.001
			44.00	45.50	D911395	1.50	<0.005		0.001
			45.50	47.00	D911396	1.50	<0.005		0.001
			47.00	48.50	D911397	1.50	<0.005		0.001
			48.50	50.00	D911398	1.50	0.006		0.006
			50.00	51.50	D911399	1.50	0.006		0.006
			51.50	53.00	D911401	1.50	<0.005		0.001
			53.00	54.50	D911402	1.50	<0.005		0.001
			54.50	56.00	D911403	1.50	<0.005		0.001
			56.00	57.50	D911404	1.50	<0.005		0.001
			57.50	59.00	D911405	1.50	<0.005		0.001
			59.00	60.50	D911406	1.50	<0.005		0.001
			60.50	62.00	D911407	1.50	<0.005		0.001
			62.00	63.50	D911408	1.50	0.005		0.005
			63.50	65.00	D911409	1.50	<0.005		0.001
			65.00	66.50	D911411	1.50	<0.005		0.001
			66.50	68.00	D911412	1.50	<0.005		0.001
			68.00	69.50	D911413	1.50	<0.005		0.001
			69.50	71.00	D911414	1.50	<0.005		0.001
			71.00	72.50	D911415	1.50	<0.005		0.001
			72.50	74.00	D911416	1.50	0.006		0.006
			74.00	75.00	202088	1.00	0.928		0.928
74.60	78.50	V3; BR; FOL <b>Mafic Meta-Volcanic ; Brecciated; Foliation</b> Same as main description, but 30% white to smokey Alb+ /+++	75.00	76.00	202089	1.00	0.064		0.064
			76.00	76.90	202090	0.90	1.560		1.560

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
76.70	77.00	BRE <b>Breccia</b> brecciated with silica flooding and 1-2% dis py.	76.90	77.70	202091	0.80	0.383	0.383
			77.70	78.50	202092	0.80	0.715	0.715
			78.50	80.00	202093	1.50	0.007	0.007
			80.00	81.50	D911417	1.50	0.012	0.012
			81.50	83.00	D911418	1.50	<0.005	0.001
			83.00	84.50	D911419	1.50	<0.005	0.001
			84.50	86.00	D911421	1.50	<0.005	0.001
			86.00	87.50	D911422	1.50	0.005	0.005
			87.50	89.00	D911423	1.50	0.006	0.006
			89.00	90.50	D911424	1.50	0.083	0.083
			90.50	92.00	D911425	1.50	0.010	0.010
			92.00	93.50	D911426	1.50	0.014	0.014
			93.50	95.00	D911427	1.50	<0.005	0.001
			95.00	96.50	202094	1.50	0.009	0.009
			96.50	98.00	202095	1.50	0.005	0.005
			98.00	99.50	202096	1.50	0.142	0.142
			99.50	101.00	202097	1.50	0.032	0.032
			101.00	102.50	D911428	1.50	<0.005	0.001
			102.50	104.00	D911429	1.50	<0.005	0.001
			104.00	105.50	D911431	1.50	<0.005	0.001
			105.50	107.00	D911432	1.50	<0.005	0.001
			107.00	108.00	D911433	1.00	<0.005	0.001
			108.00	108.90	D911434	0.90	<0.005	0.001
			108.90	109.90	202098	1.00	<0.005	0.001
109.90	111.50	I2D LT POR; BR <b>Syenite Lath Porphyry Intrusive; Brecciated</b> Green to dark green, medium to coarse grain, 30% Fract++ & K+-altered & elongated along foliation lath phenos<3.0cm long & <1.0cm wide, highly foliated@30°TCA. 5% white Alb++ VI Qtz-Carb@20-40°TCA<1.0cm. Chl++/+++, 5% buff-yellow to greensih Ser++. Tr fine diss Py.	109.90	110.70	202099	0.80	<0.005	0.001
			110.70	111.50	202101	0.80	<0.005	0.001
			111.50	112.50	202102	1.00	<0.005	0.001
			112.50	113.00	D911435	0.50	<0.005	0.001
			113.00	114.50	D911436	1.50	<0.005	0.001
			114.50	116.00	D911437	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Upper Contact@30°TCA & Lower Contact@20°TCA.	116.00	117.70	D911438	1.70	<0.005		0.001
			117.70	119.35	D911439	1.65	<0.005		0.001
			119.35	120.35	202103	1.00	<0.005		0.001
120.35	124.80	I2D LT POR; BR; FOL	120.35	121.85	202104	1.50	<0.005		0.001
		<b>Syenite Lath Porphyry Intrusive; Brecciated; Foliation</b>	121.85	123.35	202105	1.50	<0.005		0.001
		Same as 109.90-111.50m description, but Tr-1% very fine diss	123.35	124.75	202106	1.40	<0.005		0.001
		Py & Tr very fine diss Cp.	124.75	125.75	202107	1.00	<0.005		0.001
		Upper Contact@40°TCA & Lower Contact@20°TCA.	125.75	126.70	D911441	0.95	<0.005		0.001
		**Colour is dark red-green	126.70	128.00	D911442	1.30	<0.005		0.001
			128.00	129.50	D911443	1.50	<0.005		0.001
			129.50	131.00	D911444	1.50	<0.005		0.001
			131.00	132.50	D911446	1.50	<0.005		0.001
			132.50	134.00	D911447	1.50	<0.005		0.001
			134.00	135.50	202108	1.50	<0.005		0.001
			135.50	136.20	202109	0.70	<0.005		0.001
			136.20	137.00	202111	0.80	0.193		0.193
			137.00	138.20	202112	1.20	<0.005		0.001
			138.20	138.80	202113	0.60	<0.005		0.001
			138.80	139.95	202114	1.15	0.005		0.005
139.95	148.85	TZ; BR; FOL							
		<b>Transitional Zone; Brecciated; Foliation</b>							
		Green, medium to coarse grain, highly foliated@0-30°TCA. Fract++ & filled with a white to smokey Alb++ Qtz-Carb fluid, 7-10% white to smokey Alb++/+++ VI Qtz-Carb@0-50°TCA<5.0cm. Buff-yellow to greenish Ser++. 5-7% extremely to very fine diss Py up to loc 12-15%, 1% fine to coarse diss AsPy & AsPy cubes<0.1cm & Tr-1% very fine diss Cp.							
		Upper Contact@10°TCA & Lower Contact@30°TCA.							
139.95	148.85	Py07; As02; Cp0.5	139.95	141.00	202115	1.05	0.016		0.016
		<b>Pyrite 07%; Arsenopyrite 02%; Chalcopyrite 0.5%</b>	141.00	142.00	202116	1.00	1.205		1.205
		Same as 139.95-148.85 main description.	142.00	143.00	202117	1.00	1.270		1.270
			143.00	144.00	202118	1.00	0.520		0.520
			144.00	145.00	202119	1.00	0.177		0.177
			145.00	146.00	202121	1.00	0.111		0.111
			146.00	147.00	202122	1.00	0.199		0.199

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
148.85	179.30	<p>SY POR</p> <p><b>Syenite Porphyry Intrusive</b></p> <p>Greyish red to brick red to loc wine red, medium grain, 35% euhedral phenos barely visible. Fract+++ to loc. Fract++++ &amp; filled mainly with a white to smokey Alb+/+++ Qtz-Carb fluid or a dark green to black Chl. 3-5% white-smokey VI Qtz-Carb@30-70°TCA&lt;2.0cm. 1-2% extremely to very fine diss Py up to loc 10%. Upper Contact@30°TCA &amp; Lower Contact@50°TCA.</p>	147.00	148.00	202123	1.00	0.153		0.153
			148.00	148.85	202124	0.85	0.380		0.380
			148.85	150.00	202125	1.15	0.226		0.226
			150.00	151.00	202126	1.00	0.173		0.173
			151.00	152.00	202127	1.00	0.062		0.062
			152.00	153.00	202128	1.00	0.014		0.014
			153.00	154.00	202129	1.00	<0.005		0.001
			154.00	155.00	202130	1.00	0.027		0.027
			155.00	156.50	202131	1.50	<0.005		0.001
			156.50	158.00	202132	1.50	0.031		0.031
			158.00	159.50	202133	1.50	0.449		0.449
			159.50	161.00	202134	1.50	0.323		0.323
			161.00	162.00	202135	1.00	0.957		0.957
			162.00	163.00	202136	1.00	0.423		0.423
			163.00	164.00	202137	1.00	1.755		1.755
			164.00	165.00	202138	1.00	0.536		0.536
			165.00	166.00	202139	1.00	0.442		0.442
			166.00	167.00	202141	1.00	0.938		0.938
			167.00	168.50	202142	1.50	0.234		0.234
			168.50	170.00	202143	1.50	0.199		0.199
170.00	171.00	202144	1.00	0.503		0.503			
171.00	172.00	202145	1.00	0.694		0.694			
172.00	173.00	202146	1.00	0.347		0.347			
173.00	174.50	202147	1.50	0.647		0.647			
174.50	176.00	202148	1.50	0.555		0.555			
176.00	177.50	202149	1.50	0.181		0.181			
177.50	179.00	202151	1.50	0.147		0.147			
179.00	180.50	202152	1.50	3.010	2.90	2.900			
179.30	184.00	<p>TZ; I2D POR; FOL</p> <p><b>Transitional Zone; Syenite Porphyry Intrusive; Foliation</b></p> <p>Transitional syenite porphyry intrusive, greyish green to greenish reddish grey, medium to coarse grain, 30% euhedral Fld phenos barely visible&lt;0.5cm. Moderatly to highly foliated@45-55°TCA. Fract++&amp; filled with a white Alb++ &amp; K++ altered Qtz-Carb fluid. 3-5% white Alb++ VI Qtz-Carb@30-60°TCA&lt;2.0cm. Chl++/+++ 2-3% very</p>	180.50	182.00	202153	1.50	3.560	3.51	3.510
			182.00	183.00	202154	1.00	0.321		0.321
			183.00	184.00	202155	1.00	0.547		0.547

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
184.00	200.00	fine diss Py. Upper Contact@50°TCA & Lower Contact@35°TCA. BA; FOL <b>Mafic Meta-Volcanic ; Foliation</b> Green to dark green, medium grain to loc coarse grain, highly foliated@25-45°TCA & loc highly foliated@0-10°TCA. Moderatly fractured & filled with a white Alb+/+++ Qtz-Carb fluid or by a dark Chl. 2-3% white Alb+/+++ VI & V Qtz-Carb@20-50°TCA<7.0cm. 5-7% white Alb+++ Qtz-Carb specks<0.3cm. Loc buff-yellow to greenish Ser++ along fractures & foliation. Carb++ to loc Carb+++. Tr fine diss Py. Upper Contact@35°TCA.	184.00	185.00	202156	1.00	0.016		0.016
			185.00	186.50	D911448	1.50	0.006		0.006
			186.50	188.00	D911449	1.50	<0.005		0.001
			188.00	189.50	D911451	1.50	<0.005		0.001
			189.50	191.00	D911452	1.50	<0.005		0.001
			191.00	192.50	D911453	1.50	<0.005		0.001
			192.50	194.00	D911454	1.50	<0.005		0.001
			194.00	195.50	D911455	1.50	<0.005		0.001
			195.50	197.00	D911456	1.50	<0.005		0.001
			197.00	198.50	D911457	1.50	<0.005		0.001
			198.50	200.00	D911458	1.50	<0.005		0.001
200.00		Fin du sondage Nombre d'échantillons : 128 Nombre d'échantillons QAQC : 13 Longueur totale échantillonnée : 165.80							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
36.50	36.50	D911390	O54Pa	0.00	3.060	3.060
50.00	51.50	D911400	D911399	1.50	0.005	0.005
63.50	63.50	D911410	O52Pb	0.00	0.316	0.316
83.00	84.50	D911420	D911419	1.50	<0.005	0.001
102.50	102.50	D911430	O53Pb	0.00	0.647	0.647
109.90	109.90	202100	O53Pb	0.00	0.609	0.609
117.70	119.35	D911440	D911439	1.65	<0.005	0.001
129.50	129.50	D911445	m	0.00	<0.005	0.001
135.50	135.50	202110	m	0.00	<0.005	0.001
144.00	144.00	202120	O6Pc	0.00	1.540	1.540
165.00	165.00	202140	O15Pa	0.00	0.948	0.948
176.00	176.00	202150	m	0.00	<0.005	0.001
186.50	186.50	D911450	O54Pa	0.00	3.120	3.120

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-69	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multidrill	Lot :	
Décrit par : Geneviève Carignan	Du : 2009-10-20	Date de description : 2009-10-20
	Au : 2009-10-22	

Collet

Azimut : 133.96°  
 Plongée : -47.00°  
 Longueur : 183.00 m

UTM

Est	630 036.8
Nord	5 374 515.8
Élévation	280.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	33.00	145.79°	-46.61°	Non
Reflex	36.00	147.43°	-46.68°	Non
Reflex	39.00	147.66°	-46.65°	Non
Reflex	42.00	150.94°	-46.56°	Non
Reflex	45.00	149.50°	-46.27°	Non
Reflex	48.00	149.90°	-46.54°	Non
Reflex	51.00	151.46°	-46.48°	Non
Reflex	54.00	151.52°	-46.15°	Non
Reflex	57.00	148.88°	-46.07°	Oui
Reflex	60.00	150.07°	-45.78°	Non
Reflex	63.00	151.39°	-46.06°	Non
Reflex	66.00	149.91°	-45.99°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	69.00	150.61°	-45.91°	Non
Reflex	72.00	148.47°	-45.45°	Oui
Reflex	75.00	149.85°	-45.72°	Non
Reflex	78.00	150.44°	-45.59°	Non
Reflex	81.00	149.24°	-45.43°	Non
Reflex	84.00	151.01°	-45.21°	Oui
Reflex	87.00	148.68°	-45.15°	Non
Reflex	90.00	150.24°	-45.09°	Non
Reflex	93.00	149.67°	-45.01°	Non
Reflex	96.00	149.54°	-44.90°	Non
Reflex	99.00	151.98°	-44.93°	Oui
Reflex	102.00	152.96°	-44.51°	Oui

Description

NAD 83, UTM Zone 17

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	26.70	MT <b>Casing</b> Casing.							
26.70	183.00	SY POR <b>Syenite Porphyry Intrusive</b> Red-purple to green-greyish to loc grey fine grained Syenite Porphyry Intrusive. 7-10%(up to 20%) chloritized Fp phenos (0.2-1cm). Fract++ to loc Fract+++ filled with Ca-Qtz or Alb or Chl @ 50-60° TCA. Loc Bre++ with angular syenite fragments in a Qtz-Ca-Alb matrix. 1-2% smokey Qtz veins @ 40-50° TCA. Massive to loc foliated @ 40-60° TCA. Heterogenous and loc magnetic.  Light to moderate chloritisation (fractures filling and pervasive), ligh carbonatisation (fractures filling) and light to loc moderate silicification (pervasive).  Traces to loc 1% (up to 6%) very fine disseminated pyrite.	26.70	28.00	207887	1.30	1.270		1.270
27.30	31.50	Car; Sil <b>Carbonatisation; Silicification</b> Moderate pervasive silicification and moderate fracture filling carbonatisation. Gradual contacts.							
27.30	31.50	Py04 <b>Pyrite 04%</b> 3-5% very fine disseminated pyrite in a grey silicified and carbonatized brecciated syenite.	28.00	30.00	207888	2.00	0.871		0.871
			30.00	32.00	207889	2.00	1.705		1.705
			32.00	34.00	207891	2.00	0.184		0.184
			34.00	36.00	207892	2.00	0.438		0.438
			36.00	38.00	207893	2.00	0.671		0.671
37.50	37.70	Py05 <b>Pyrite 05%</b> 4-6% very fine disseminated pyrite in a silicified and Fract+++ zone with gradual contacts.	38.00	40.00	207894	2.00	0.674		0.674
			40.00	42.00	207896	2.00	1.080		1.080
41.40	45.30	Car; Sil; Alb <b>Carbonatisation; Silicification; Albitisation</b> Moderate pervasive silicification and moderate fracture filling carbonatisation. Light albitisation in fractures. Gradual contacts.							
41.40	45.30	Py05 <b>Pyrite 05%</b> 4-6% very fine disseminated pyrite in a grey silicified,	42.00	44.00	207897	2.00	1.770		1.770
			44.00	46.00	207898	2.00	1.405		1.405



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
		carbonatized and albitized brecciated syenite.	46.00	48.00	207899	2.00		0.112		0.112
			48.00	50.00	207900	2.00		0.035		0.035
49.50	52.00	Chl	50.00	52.00	207901	2.00		0.147		0.147
		<b>Chloritisation</b>	52.00	54.00	207902	2.00		0.348		0.348
		Moderate to high pervasive and in veins chloritisation. Gradual contacts.	54.00	56.00	207903	2.00		0.200		0.200
			56.00	58.00	207904	2.00		0.119		0.119
			58.00	60.00	207905	2.00		0.177		0.177
			60.00	62.00	207906	2.00		0.219		0.219
			62.00	64.00	207907	2.00		0.341		0.341
			64.00	66.00	207908	2.00		0.105		0.105
			66.00	68.00	207909	2.00		0.056		0.056
66.50	67.80	BRE	68.00	70.00	207910	2.00		0.152		0.152
		<b>Breccia</b>	70.00	72.00	207911	2.00		0.053		0.053
		Brecciated salmon colored syenite. Angular syenite fragments with chlorite filling the fractures.	72.00	74.00	207912	2.00		0.056		0.056
			74.00	76.00	207913	2.00		0.083		0.083
74.20	74.65	STW;80%;QzClCb;;;	76.00	78.00	207914	2.00		0.234		0.234
		<b>Stockwerk 80% Quartz Chlorite Carbonate</b>	78.00	79.50	207916	1.50		0.104		0.104
		Quartz-Carbonates-Chlorite stockwerk.	79.50	81.00	207917	1.50		0.189		0.189
			81.00	82.50	207918	1.50		0.140		0.140
81.10	81.35	BRE	82.50	84.00	207919	1.50		0.536		0.536
		<b>Breccia</b>	84.00	85.50	207921	1.50		0.421		0.421
		Angular syenite fragments (smaller than 5cm) with chlorite filling the fractures.								
84.10	98.70	Chl	85.50	87.00	207922	1.50		0.091		0.091
		<b>Chloritisation</b>	87.00	88.50	207923	1.50		0.007		0.007
		Moderate pervasive chloritisation.	88.50	90.00	207924	1.50		0.025		0.025
			90.00	91.50	207925	1.50		0.020		0.020
			91.50	93.00	207926	1.50		0.122		0.122
			93.00	94.50	207927	1.50		0.148		0.148
			94.50	96.00	207928	1.50		0.251		0.251
			96.00	97.50	207929	1.50		0.200		0.200
			97.50	99.00	207930	1.50		0.070		0.070
			99.00	100.50	207931	1.50		0.037		0.037
			100.50	102.00	207932	1.50		0.039		0.039

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
105.20	105.60	BRE <b>Breccia</b> Angular syenite fragments in an albite-qtz matrix.	102.00	103.50	207933	1.50	0.011		0.011	
			103.50	105.00	207934	1.50	0.053		0.053	
			105.00	106.50	207936	1.50	0.024		0.024	
			106.50	108.00	207937	1.50	1.935		1.935	
106.80	107.70	Py03 <b>Pyrite 03%</b> 2-4% very fine disseminated pyrite associated with silicification zones.	108.00	109.50	207938	1.50	0.441		0.441	
109.20	154.70	Si; Chl; Car <b>Silicification; Chloritisation; Carbonatisation</b> High pervasive silicification with low to moderate carbonatisation (veinlets @ 60-70° TCA) and light chloritisation (stockwerk).  151.2-151.9m: High Carbonatisation as veinlets @ 40-50° TCA.								
109.20	170.80	Py07 <b>Pyrite 07%</b> 5-8% (up to 10%) of very fine disseminated pyrite and in veinlets in a grey silicified (high silicification) BRE+ syenite. No sharp contacts.	109.50	111.00	207939	1.50	0.028		0.028	
			111.00	112.50	207940	1.50	0.193		0.193	
			112.50	114.00	207941	1.50	0.247		0.247	
			114.00	115.50	207942	1.50	0.136		0.136	
			115.50	117.00	207943	1.50	3.340		3.37	3.370
			117.00	118.50	207944	1.50	2.410			2.410
			118.50	120.00	207945	1.50	7.100		7.14	7.140
			120.00	121.50	207946	1.50	6.920		7.11	7.110
			121.50	123.00	207947	1.50	6.120		6.19	6.190
			123.00	124.50	207948	1.50	3.320		3.30	3.300
			124.50	126.00	207949	1.50	4.560		4.70	4.700
			126.00	127.50	207951	1.50	2.710			2.710
			127.50	129.00	207952	1.50	2.810			2.810
			129.00	130.50	207953	1.50	2.430			2.430
133.60	134.00	BC <b>Broken core</b> Broken core (~5cm each).	130.50	132.00	207954	1.50	2.400		2.400	
			132.00	133.50	207956	1.50	4.070	3.53	3.530	
			133.50	135.00	207957	1.50	1.325		1.325	
			135.00	136.50	207958	1.50	1.500		1.500	
			136.50	138.00	207959	1.50	1.300		1.300	

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				138.00	139.50	207960	1.50	0.636		0.636
				139.50	141.00	207961	1.50	1.255		1.255
				141.00	142.50	228922	1.50	2.700		2.700
				142.50	144.00	228923	1.50	2.190		2.190
				144.00	145.50	228924	1.50	2.070		2.070
				145.50	147.00	228925	1.50	1.760		1.760
				147.00	148.50	228926	1.50	1.590		1.590
				148.50	150.00	228927	1.50	1.735		1.735
				150.00	151.50	228928	1.50	3.340	3.32	3.320
				151.50	153.00	228929	1.50	2.560		2.560
				153.00	154.50	228930	1.50	1.035		1.035
				154.50	156.00	228931	1.50	1.395		1.395
154.70	170.80	Sil; Chl		156.00	157.50	228932	1.50	0.950		0.950
		<b>Silicification; Chloritisation</b>		157.50	159.00	228933	1.50	1.050		1.050
		Light to moderate silicification (pervasive and veins @ 50-60		159.00	160.50	228935	1.50	0.768		0.768
		TCA) and light chloritisation (stringers).		160.50	162.00	228936	1.50	1.210		1.210
				162.00	163.50	228937	1.50	0.653		0.653
				163.50	165.00	228938	1.50	0.520		0.520
				165.00	166.50	228939	1.50	0.456		0.456
				166.50	168.00	228941	1.50	1.450		1.450
				168.00	169.50	228942	1.50	0.882		0.882
				169.50	171.00	207983	1.50	0.863		0.863
170.80	171.40	BRE		171.00	172.50	207984	1.50	0.114		0.114
		<b>Breccia</b>		172.50	174.00	207985	1.50	0.141		0.141
		Syenite fragments with chlorite-carbonates filling.		174.00	175.50	207986	1.50	0.195		0.195
				175.50	177.00	207987	1.50	1.105		1.105
				177.00	178.50	207988	1.50	1.225		1.225
				178.50	180.00	207989	1.50	0.156		0.156
				180.00	181.50	207990	1.50	0.095		0.095
				181.50	183.00	207991	1.50	0.035		0.035
183.00	Fin du sondage									
	Nombre d'échantillons : 96									
	Nombre d'échantillons QAQC : 10									
	Longueur totale échantillonnée : 156.30									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
30.00	32.00	207890	m	2.00	0.006	0.006
38.00	40.00	207895	O15Pa	2.00	1.020	1.020
76.00	78.00	207915	O6Pc	2.00	1.560	1.560
82.50	84.00	207920	m	1.50	<0.005	0.001
103.50	105.00	207935	O54Pa	1.50	2.940	2.940
124.50	126.00	207950	m	1.50	0.010	0.010
130.50	132.00	207955	O50Pb	1.50	0.859	0.859
151.50	153.00	207970	m	1.50	0.009	0.009
157.50	159.00	228934	O54Pa	1.50	2.940	2.940
165.00	166.50	228940	228939	1.50	0.469	0.469

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-70

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie

Foré par : Foramex

Lot :

Décrit par : C. Gagnier

Du : 2009-10-20

Date de description : 2009-10-21

Au : 2009-10-21

Collet

UTM

Azimut : 149.43°

Plongée : -44.90°

Longueur : 151.00 m

Est 630 780.1

Nord 5 374 383.7

Élévation 311.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	10.00	159.89°	-44.90°	Oui
Reflex	13.00	163.17°	-44.56°	Non
Reflex	16.00	163.02°	-44.61°	Non
Reflex	19.00	163.28°	-44.63°	Non
Reflex	22.00	163.50°	-44.57°	Non
Reflex	25.00	163.61°	-44.50°	Non
Reflex	28.00	162.88°	-44.45°	Non
Reflex	31.00	163.43°	-44.61°	Non
Reflex	34.00	163.49°	-44.41°	Non
Reflex	37.00	163.61°	-44.61°	Non
Reflex	40.00	164.10°	-44.55°	Non
Reflex	43.00	163.47°	-44.41°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	46.00	163.80°	-44.46°	Non
Reflex	49.00	163.64°	-44.46°	Non
Reflex	52.00	164.66°	-44.60°	Non
Reflex	55.00	163.87°	-44.50°	Non
Reflex	58.00	164.13°	-44.48°	Non
Reflex	61.00	164.99°	-44.63°	Non
Reflex	64.00	164.02°	-44.52°	Non
Reflex	67.00	164.48°	-44.50°	Non
Reflex	70.00	165.29°	-44.54°	Non
Reflex	73.00	164.86°	-44.68°	Non
Reflex	76.00	164.27°	-44.51°	Non
Reflex	79.00	164.76°	-44.54°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Both single shots and multi-shot were corrected for magnetic declination (12.5 degrees to the west).

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	37.50	SY <b>Syenite</b> The drilling started right into the outcrop. Casing of 1.5m. Of the 1.5m of the casing length, 0.32m of core have been recovered, logged and sampled. Red brick to greenish, felsic, mottled aphanitic intrusive with less than 1% of 3mm to 8mm white to cream colored (with rims of green chlorite) anhedral feldspar phenocrystals. The green coloration (chloritization) is more intense near to millimetric quartz-feldspar tension veins at 60 TCA: both walls are chloritized over several decimeters. Locally mineralized with fine pyrite (0.5 to 1%). Locally brecciated. Cross-cutted by 0.5% to 2% of thin, millimetric white carbonate veinlets generally at 60 TCA. Gradational lower contact over 50cm.	0.00	1.50	P009504	1.50	<0.005		0.001
0.00	13.00	VEI;QzFp;T;60°;Py0.1; <b>Vein Quartz Feldspath (alkaline) Tension 60°</b> <b>Pyrite 0.1%</b> Less than 1% of millimetric (1 to 10mm) quartz-feldspar veinlets generally at 60 TCA.							
1.50	16.40	Chl <b>Chloritisation</b> Pervasive chloritization often associated to thin quartz/feldspar millimetric veinlets generally at 60 TCA.	1.50	3.00	208101	1.50	0.005		0.005
			3.00	4.50	208102	1.50	0.006		0.006
			4.50	6.00	208103	1.50	<0.005		0.001
			6.00	7.50	208104	1.50	0.011		0.011
7.20	8.80	BC <b>Broken core</b> RQD=0.	7.50	9.00	208105	1.50	<0.005		0.001
8.80	31.50	O; BRE <b>Lamination 45°; Breccia</b> Lamination made by chlorite shreds. Locally brecciated.	9.00	10.50	208106	1.50	0.007		0.007
			10.50	12.00	208107	1.50	0.011		0.011
			12.00	13.50	208108	1.50	0.016		0.016
13.25	14.10	Py0.5 <b>Pyrite 0.5%</b> Finely disseminated euhedral pyrite.	13.50	15.00	208109	1.50	0.017		0.017
			15.00	16.50	208110	1.50	0.006		0.006
16.40	16.80	Sil <b>Silicification</b> Purple, cherty silicification with blurred contacts.	16.50	18.00	208111	1.50	0.087		0.087
16.80	22.70	Chl <b>Chloritisation</b> Green chlorite shreds at 60 TCA.							
16.90	17.05	Py01	18.00	19.50	208112	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Pyrite 01%</b> Very fine pyrite.	19.50	21.00	208113	1.50	0.008		0.008
			21.00	22.50	208114	1.50	0.091		0.091
			22.50	24.00	208116	1.50	0.057		0.057
22.70	39.30	Wea; Chl	24.00	25.50	208117	1.50	0.053		0.053
		<b>Weathering (Incl. Saprolitic alter.); Chloritisation</b> Locally brown colored, hematized. Otherwise chloritized.	25.50	27.00	208118	1.50	0.036		0.036
			27.00	28.50	208119	1.50	0.056		0.056
			28.50	30.00	208121	1.50	0.008		0.008
			30.00	31.50	208122	1.50	0.009		0.009
31.50	36.90	FRC	31.50	33.00	208123	1.50	0.034		0.034
		<b>Fractured</b> RQD=50%. Locally fractured.	33.00	34.50	208124	1.50	0.174		0.174
			34.50	36.00	208125	1.50	0.957		0.957
			36.00	37.50	208126	1.50	0.572		0.572
36.90	41.70	BRE <b>Breccia</b>							
37.50	52.30	SY; MNZD <b>Syenite; Mineralized</b> RW ZONE. Gradational contacts over 50cm. Grey to greenish, mineralized, strongly altered (silicified, sericitized, carbonated, chloritized), locally brecciated syenite. ).1% to up to 7% of fine pyrite in the matrix. Locally cross-cutted by 0.1% of thin, very dark green chlorite anastomosed, hairlike chlorite veinlets.							
37.50	51.30	LT POR <b>Lath porphyry</b> Mineralized, red brick to greenish, sericitized lath porphyry with 30% of 1-3cm long feldspar phenocrystals oriented at 60 TCA. 0.5% to up to 7% of very fine pyrite in the matrix.							
37.50	52.30	Py01 <b>Pyrite 01%</b> RW ZONE. Brecciated zone, locally mineralized with 0.1 to up to 7% of very fine pyrite in the matrix. Locally 0.1% if thin, hairlike black to dark greenish chlorite anastomosed veinlets. The content in pyrite varies a lot from a spot to another. However, the concentration in pyrite is directly proportional to the sericite alteration.	37.50	39.50	208127	2.00	0.347		0.347

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
39.30	51.30	Chl; Ser <b>Chloritisation; Sericitisation</b> Greenish alteration: mix of sericite ? and chlorite ?	39.50	41.50	208128	2.00	0.072		0.072
			41.50	43.50	208129	2.00	0.229		0.229
			43.50	45.50	208130	2.00	0.572		0.572
			45.50	47.50	208131	2.00	1.555		1.555
			47.50	49.50	208132	2.00	0.230		0.230
			49.50	51.50	208133	2.00	0.544		0.544
			51.50	53.50	208134	2.00	0.241		0.241
52.30	97.90	SY <b>Syenite</b> Gradational contacts over 50cm. Red brick to greenish, felsic, mottled aphanitic intrusive with less than 1% of 3mm to 8mm white to cream colored (with rims of green chlorite) anhedral feldspar phenocrystals. The green coloration (chloritization) is more intense near to millimetric quartz-feldspar tension veins at 60 TCA: both walls are chloritized over several decimeters. Locally mineralized with fine pyrite (0.5 to 1%). Locally brecciated. Cross-cutted by 0.5% to 2% of thin, millimetric white carbonate veinlets generally at 60 TCA.	53.50	55.50	208136	2.00	0.172		0.172
			55.50	57.50	208137	2.00	0.109		0.109
			57.50	59.50	208138	2.00	0.014		0.014
			59.50	61.00	208139	1.50	0.059		0.059
			61.00	62.60	208141	1.60	0.017		0.017
			62.60	64.00	208142	1.40	0.012		0.012
			64.00	65.50	208143	1.50	0.084		0.084
			65.50	67.00	208144	1.50	0.026		0.026
			67.00	68.50	208145	1.50	0.022		0.022
			68.50	70.00	208146	1.50	0.005		0.005
			70.00	71.50	208147	1.50	0.007		0.007
			71.50	73.00	208148	1.50	0.015		0.015
			73.00	74.50	208149	1.50	0.008		0.008
			74.50	76.00	208150	1.50	0.033		0.033
76.00	77.50	208151	1.50	0.016		0.016			
76.90	97.90	Chl <b>Chloritisation</b> Gradational contacts over 50cm. Greenish pervasive chloritization.	77.50	79.00	P009498	1.50	0.006		0.006
78.00	83.00	VEI; QzCbCl; 50°; Py0.2; <b>Vein Quartz Carbonate Chlorite 50° Pyrite 0.2%</b> 5% of 1cm white quartz-carbonate-chlorite veins at 50 to 80 TCA. Locally up to 2% of fine, euhedral pyrite on both walls. Average of 0.2% of pyrite	79.00	80.50	P009499	1.50	0.192		0.192
			80.50	82.00	P009500	1.50	0.155		0.155
81.50	83.00	Py0.5 <b>Pyrite 0.5%</b> Weakly mineralized zone (0.5% but very locally up to 2% of euhedral pyrite) associated to a higher concentration of	82.00	83.50	P009502	1.50	0.628		0.628
			83.50	85.00	P009503	1.50	0.016		0.016
			85.00	86.50	P009505	1.50	0.070		0.070
			86.50	88.00	P009506	1.50	0.039		0.039



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
		quartz-carbonate-chlorite veins.	88.00	89.50	P009507	1.50		0.015		0.015
			89.50	91.00	P009508	1.50		0.016		0.016
			91.00	92.50	P009509	1.50		0.028		0.028
			92.50	94.00	P009510	1.50		0.033		0.033
			94.00	95.50	P009511	1.50		0.048		0.048
			95.50	97.00	P009512	1.50		0.050		0.050
			97.00	98.50	P009513	1.50		0.039		0.039
97.90	110.40	SY; MNZD <b>Syenite; Mineralized</b> RS ZONE. Gradational upper contact over 50cm. Grey to greenish to purple mineralized porphyry syenite with 5 to 10% of 2mm to 5mm anhedral, grey to greenish (chloritized) feldspar phenocrysts. 3% of white, 1-3mm carbonates veinlets at 60 TCA. Strongly silicified and sericitized, moderately carbonated and albitized. Mineralized with 1 to 7% of very fine pyrite (average of 3% pyrite). Sharp lower contact at 70 TCA.								
97.90	110.40	Sil; Ser; Car; Alb <b>Silicification; Sericitisation; Carbonatisation; Albitisation</b> Strong silicification and sericitization. Also carbonated and albitized.								
97.90	110.40	BRE <b>Breccia</b> Locally brecciated.								
97.90	110.40	Py03 <b>Pyrite 03%</b> RS ZONE. Highly mineralized yet with a very variable content in fine pyrite: from 0.5 to up to 7% (average: 3%).								
97.90	110.40	VE1;2;Cb;;60°; <b>Vein 2 Carbonate 60°</b> About 3% of thin (1 to 3mm) white carbonate veins at 60 TCA.	98.50	100.00	P009514	1.50		0.683		0.683
			100.00	101.50	208170	1.50		0.114		0.114
			101.50	103.00	208171	1.50		0.384		0.384
			103.00	104.50	208172	1.50		1.975		1.975
			104.50	106.00	208173	1.50		0.839		0.839
			106.00	107.50	208174	1.50		1.135		1.135
			107.50	109.00	208176	1.50		1.100		1.100
			109.00	110.40	208177	1.40		1.395		1.395

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
110.40	115.40	FOL <b>Foliation</b> Sharp , intrusive upper contact at 70 TCA. Transitional zone between the syenite and the gabbro (a cooked margin of the gabbro intruded by the felsic intrusion). Well foliated (at 60 TCA.) light green gabbro ? or a bleached syenite ? 2% of apple green chlorite shards. 3% of light yellow leucoxene. Not mineralized.						
110.40	115.40	Chl <b>Chloritisation</b> Strongly chloritized.						
110.40	115.40	FOL <b>Foliation 60°</b>	110.40	112.00	208178	1.60	0.094	0.094
			112.00	113.50	208179	1.50	0.272	0.272
			113.50	115.40	208181	1.90	0.087	0.087
115.40	151.00	GA; MAS <b>Gabbro; Massive rock</b> Gradational upper contact over 20cm. Dark green fine grain gabbro (dolerite), rather massive, not magnetic with 3% of anhedral, light yellow leucoxene. Strongly chloritized. Not mineralized.  END OF HOLE at 151m.						
115.40	151.00	Chl <b>Chloritisation</b> Strong, pervasive chloritization.	115.40	116.50	208182	1.10	0.006	0.006
			116.50	118.00	208183	1.50	<0.005	0.001
			118.00	119.50	208184	1.50	0.006	0.006
			119.50	121.00	208185	1.50	0.011	0.011
			121.00	122.50	208186	1.50	0.006	0.006
			122.50	124.00	208187	1.50	0.007	0.007
			124.00	125.70	208188	1.70	0.006	0.006
			125.70	127.00	208189	1.30	0.058	0.058
			127.00	128.50	208190	1.50	0.163	0.163
			128.50	130.00	208191	1.50	0.008	0.008
			130.00	131.50	208192	1.50	0.005	0.005
			131.50	133.00	208193	1.50	0.005	0.005
			133.00	134.50	208194	1.50	<0.005	0.001
			134.50	136.00	208196	1.50	0.006	0.006
			136.00	137.50	208197	1.50	0.005	0.005
			137.50	139.00	208198	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	139.00	140.50	208199	1.50	0.007		0.007
	140.50	142.00	208201	1.50	0.007		0.007
	142.00	143.50	208202	1.50	0.016		0.016
	143.50	145.00	208203	1.50	0.777		0.777
	145.00	146.50	208204	1.50	0.069		0.069
	146.50	148.00	208205	1.50	0.006		0.006
	148.00	149.50	208206	1.50	0.006		0.006
	149.50	151.00	208207	1.50	0.006		0.006
151.00	Fin du sondage Nombre d'échantillons : 97 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 151.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
22.50	22.50	208115	O15Pa	0.00	1.045	1.045
28.50	28.50	208120	m	0.00	<0.005	0.001
53.50	53.50	208135	O6Pc	0.00	1.670	1.670
61.00	61.00	208140	m	0.00	0.007	0.007
82.00	82.00	208155	O54Pa	0.00	0.129	0.129
86.50	86.50	208160	m	0.00	<0.005	0.001
107.50	107.50	208175	O50Pb	0.00	0.876	0.876
113.50	113.50	208180	m	0.00	0.006	0.006
134.50	134.50	208195	O61d	0.00	5.080	4.760
140.50	140.50	208200	m	0.00	0.008	0.008

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-71

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie Mine site

Foré par : Foramex

Lot :

Décrit par : C. Gagnier

Du : 2009-10-22

Date de description : 2009-10-27

Au : 2009-10-24

Collet

Azimut : 149.35°  
 Plongée : -54.80°  
 Longueur : 189.00 m

UTM

Est	630 770.5
Nord	5 374 397.5
Élévation	312.1

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	149.35°	-55.03°	Non
Reflex	5.00	149.42°	-55.01°	Non
Reflex	10.00	149.49°	-54.99°	Non
Reflex	15.00	149.71°	-54.93°	Non
Reflex	20.00	150.01°	-54.91°	Non
Reflex	25.00	150.11°	-54.89°	Non
Reflex	30.00	150.18°	-54.89°	Non
Reflex	35.00	150.30°	-54.79°	Non
Reflex	40.00	150.61°	-54.60°	Non
Reflex	45.00	150.87°	-54.48°	Non
Reflex	50.00	150.85°	-54.45°	Non
Reflex	55.00	150.83°	-54.42°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	60.00	150.91°	-54.41°	Non
Reflex	65.00	150.98°	-54.40°	Non
Reflex	70.00	151.09°	-54.40°	Non
Reflex	75.00	151.17°	-54.40°	Non
Reflex	80.00	151.25°	-54.39°	Non
Reflex	85.00	151.17°	-54.36°	Non
Reflex	90.00	151.24°	-54.36°	Non
Reflex	95.00	151.40°	-54.36°	Non
Reflex	100.00	151.36°	-54.37°	Non
Reflex	105.00	151.46°	-54.37°	Non
Reflex	110.00	151.52°	-54.36°	Non
Reflex	115.00	151.62°	-54.30°	Non

Description

GPS Datum NAD83, UTM Zone 17.

No multi-shot test has been done for this hole.

The single-shot tests were corrected for magnetic declination (12.5 degrees to the west).

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	120.00	151.83°	-54.17°	Non					
Reflex	125.00	151.98°	-54.15°	Non					
Reflex	130.00	152.08°	-54.17°	Non					
Reflex	135.00	152.03°	-54.16°	Non					
Reflex	140.00	152.22°	-54.12°	Non					
Reflex	145.00	152.30°	-54.11°	Non					
Reflex	150.00	152.46°	-54.13°	Non					
Reflex	155.00	152.72°	-54.17°	Non					
Reflex	160.00	152.84°	-54.11°	Non					
Reflex	165.00	152.98°	-54.03°	Non					
Reflex	170.00	153.19°	-53.99°	Non					
Reflex	175.00	153.31°	-53.95°	Non					
Reflex	180.00	153.47°	-53.90°	Non					
Reflex	185.00	153.59°	-53.86°	Non					
Reflex	189.00	153.63°	-53.83°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.50	MT <b>Casing</b> Casing						
5.50	22.20	SY <b>Syenite</b> Red to greenish, mottled porphyry syenite with locally up to 10% of anhedral, often chloritized 2-8mm feldspar phenocrysts. Locally weathered (rusty) along the fractures. Locally magnetic. Not mineralized. 1% of millimetric, white to cream carbonate and quartz veinlets generally at 60 TCA. Gradational lower contact over 20cm.						
5.50	22.20	Chl; Wea <b>Chloritisation; Weathering (Incl. Saproplitic alter.)</b>	5.50	7.25	208208	1.75	0.023	0.023
			7.25	9.00	208209	1.75	0.019	0.019
			9.00	10.50	208210	1.50	0.005	0.005
			10.50	12.00	208211	1.50	0.055	0.055
			12.00	13.50	208212	1.50	0.029	0.029
			13.50	15.00	208213	1.50	0.430	0.430
			15.00	16.50	208214	1.50	0.126	0.126
			16.50	18.00	208216	1.50	0.092	0.092
			18.00	19.50	208217	1.50	0.064	0.064
			19.50	21.00	208218	1.50	0.015	0.015
			21.00	22.20	208219	1.20	0.030	0.030
22.20	27.50	SY; MNZD <b>Syenite; Mineralized</b> RW ZONE ? Gradational contacts over 20cm. Mineralized, red to greenish mottled syenite becoming increasingly sericitized, carbonatized and silicified. 1% of millimetric, white carbonate veinlets generally at 60 TCA.						
22.20	27.50	Ser; Car; Sil <b>Sericitisation; Carbonatisation; Silicification</b> Moderately altered, mineralized zone.	22.20	24.00	208221	1.80	0.094	0.094
22.20	25.00	Py01 <b>Pyrite 01%</b> RW ZONE ? 1% of euhedral pyrite.						
23.55	24.50	VEI;;QzCb;;;Py01; <b>Vein Quartz Carbonate Pyrite01%</b> 10% of 1-5cm quartz-carbonate veins at 80 TCA.	24.00	25.50	208222	1.50	0.642	0.642
			25.50	27.50	208223	2.00	0.042	0.042
27.50	38.80	SY; MAS						

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
<p><b>Syenite; Massive rock</b> Gradational contacts over 20cm. Red to greenish, barren, massive, locally mottled with aphanitic matrix and less than 5% of anhedral, chloritized, 3-8mm feldspar phenocrystals. 1% of fine white to cream carbonate and chlorite veinlets generally at 60 TCA. Not magnetic.</p>								
27.50	38.80	Chl	27.50	28.50	208224	1.00	0.008	0.008
		<b>Chloritisation</b>	28.50	30.00	208225	1.50	0.005	0.005
		Weak chloritization.	30.00	31.50	208226	1.50	0.007	0.007
			31.50	33.00	208227	1.50	<0.005	0.001
			33.00	34.50	208228	1.50	0.009	0.009
			34.50	36.00	208229	1.50	0.007	0.007
			36.00	37.50	208230	1.50	0.005	0.005
			37.50	38.80	208231	1.30	0.057	0.057
38.80	48.20	SY; MNZD						
<p><b>Syenite 50°; Mineralized</b> Gradational contacts over 20cm. Light green (sericitized), well foliated, mineralized syenite. Cross-cutted by 5% of quartz and carbonate 1cm veins at 50 TCA.</p>								
38.80	48.20	Ser						
		<b>Sericitisation</b>						
		Strong sericitization: apple green color.						
38.80	48.20	Py01	38.80	40.50	208232	1.70	0.018	0.018
		<b>Pyrite 01%</b>	40.50	42.00	208233	1.50	0.020	0.020
		Mineralized and sericitized zone: 0.5 to 2? of euhedral pyrite.						
41.40	43.50	VEI;;QzCb;;50°;Py01;	42.00	43.50	208234	1.50	0.567	0.567
		<b>Vein Quartz Carbonate 50° Pyrite01%</b>	43.50	45.00	208236	1.50	2.850	2.850
		15% of centimetric quartz-carbonate veins at 50 TCA (locally contorted).	45.00	46.50	208237	1.50	0.038	0.038
			46.50	48.20	208238	1.70	0.041	0.041
48.20	99.40	SY; MAS	48.20	49.50	208239	1.30	0.022	0.022
<p><b>Syenite; Massive rock</b> Gradational upper contact over 20cm. Red brick, massive, mottled, weakly chloritized syenite with less than 5% of anhedral, cream colored, chloritized feldspar phenocrystals up to 1cm long. 2% of millimetric, anastomosed, white carbonate veinlets. Not mineralized. Not magnetic. Sharp lower contact at 30 TCA.</p>								
			49.50	51.00	208241	1.50	0.007	0.007
			51.00	52.50	208242	1.50	0.007	0.007
			52.50	54.00	208243	1.50	0.008	0.008
			54.00	55.50	208244	1.50	0.007	0.007
			55.50	57.00	208245	1.50	0.137	0.137
			57.00	58.50	208246	1.50	0.007	0.007
			58.50	60.00	208247	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			60.00	61.50	208248	1.50		0.007	0.007
			61.50	63.00	208249	1.50		<0.005	0.001
			63.00	64.50	208250	1.50		<0.005	0.001
			64.50	66.00	208251	1.50		<0.005	0.001
			66.00	67.40	208252	1.40		0.010	0.010
48.20	66.50	Chl <b>Chloritisation</b> Weak pervasive chloritization.							
66.50	68.50	Ser; Chl <b>Sericitisation; Chloritisation</b> Apple-green sericitized and chloritized zone. well foliated at 30 TCA. Gradational contacts over 10cm.	67.40	69.00	208253	1.60		0.032	0.032
66.50	67.40	FOL <b>Foliation 30°</b> Good foliation at 30 TCA.							
68.00	75.10	FOL <b>Foliation 40°</b> Foliation made by chlorite laminas.	69.00	70.50	208254	1.50		0.028	0.028
			70.50	72.00	208256	1.50		<0.005	0.001
			72.00	73.50	208257	1.50		0.186	0.186
			73.50	75.00	208258	1.50		0.154	0.154
			75.00	76.50	208259	1.50		0.190	0.190
75.10	81.20	LT POR; FOL <b>Lath porphyry 40°; Foliation</b> Sharp contacts at 40 TCA. Red brick, locally greenish (chloritized) lath porphyry syenite with 10 to 40% white, 0.5 to 1.5cm long feldspar lath phenocrystals oriented at 40 TCA. Locally mineralized with fine pyrite.							
75.80	76.70	Py0.75 <b>Pyrite 0.75%</b> Gradational contacts over 20cm. Mineralized zone with 0.5 to 1% of fine pyrite in the matrix.	76.50	78.00	208261	1.50		0.302	0.302
78.00	79.40	Py02 <b>Pyrite 02%</b> Gradational contacts over 20cm. Mineralized zone with 0.5 to up to 3% of fine pyrite.	78.00	79.50	208262	1.50		0.479	0.479
			79.50	81.00	208263	1.50		0.015	0.015
			81.00	82.50	208264	1.50		0.330	0.330
81.20	82.20	FW <b>Elongated Fragments 40°</b> Foliation made by the oriented lath porphyry.	82.50	84.00	208265	1.50		0.439	0.439
			84.00	85.50	208266	1.50		<0.005	0.001
			85.50	87.00	208267	1.50		0.258	0.258

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			87.00	88.70	208268	1.70	0.022		0.022
			88.70	90.00	208269	1.30	0.020		0.020
			90.00	91.50	208270	1.50	0.007		0.007
			91.50	93.00	208271	1.50	<0.005		0.001
			93.00	94.50	208272	1.50	0.016		0.016
			94.50	96.00	208273	1.50	0.037		0.037
			96.00	97.50	208274	1.50	0.620		0.620
			97.50	99.00	208276	1.50	0.005		0.005
			99.00	100.50	208277	1.50	0.137		0.137
			100.50	102.00	208278	1.50	0.006		0.006
99.40	121.70								
		SY; MNZD							
		<b>Syenite 30°; Mineralized</b>							
		Sharp upper contact made by white carbonate veins at 30 TCA. Grey to greenish, locally silicified, sericitized, carbonatized and locally mineralized mottled syenite. 5% of white, 0.5 to 3cm quartz-carbonate veins at 40 Gradational lower contact over 50cm.	102.00	103.50	208279	1.50	<0.005		0.001
			103.50	105.00	208281	1.50	0.069		0.069
			105.00	106.50	208282	1.50	0.339		0.339
99.40	110.20	Sil; Ser; Car							
		<b>Silicification; Sericitisation; Carbonatisation</b>							
99.40	99.70	Py01							
		<b>Pyrite 01%</b>							
		Upper contact of a mineralized unit. 1% of fine pyrite with 45% of anastomosed carbonate veinlets.							
99.40	109.50	VEI;;Cb;T;30°;;							
		<b>Vein Carbonate Tension 30°</b>							
		5% of thin, white millimetric carbonate (dolomite-ankerite) veinlets at 30 TCA with 1% of quartz 1-5cm white quartz veins at 30 TCA.							
106.30	107.70	Py03	106.50	108.00	208283	1.50	2.210		2.210
		<b>Pyrite 03%</b>							
		2 to 3% of fine pyrite in a grey colored, strongly silicified, sericitized and carbonatized zone.	108.00	109.50	208284	1.50	0.024		0.024
			109.50	111.00	208285	1.50	0.015		0.015
110.20	152.50	Chl							
		<b>Chloritisation</b>							
		Weak chloritization.							
111.00	127.50	Py0.5	111.00	112.50	208286	1.50	0.073		0.073
		<b>Pyrite 0.5%</b>							
		Locally mineralized with 0.5% to 1% fine or coarse euhedral pyrite.	112.50	114.00	208287	1.50	0.015		0.015
			114.00	115.50	208288	1.50	0.041		0.041

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
114.40	115.40	VEI;;QzCb;;40°;; <b>Vein Quartz Carbonate 40°</b> 15% of colorless quartz and white carbonate 1cm veins between 20 and 50 TCA. At least 2 differents generations involved.	115.50	117.00	208289	1.50	0.042		0.042
			117.00	118.50	208290	1.50	0.068		0.068
			118.50	120.00	208291	1.50	0.130		0.130
			120.00	121.50	208292	1.50	0.009		0.009
			121.50	123.00	208293	1.50	0.007		0.007
121.70	153.50	SY; POR <b>Syenite; Porphyric</b> Gradational upper contact over 50cm. Red brick, locally porphyric (otherwise mottled) syenite with 5% of 0.3 to 1cm anhedral, chlorite rimmed feldspar phenocrystals. Weakly chloritized. The last meter is apple-green (strongly chloritized), cross-cutted by 5% of pink carbonate stockwork veinlets, well laminated parallel to the lower contact and Sharp lower contact at 40 TCA.	123.00	124.50	208294	1.50	0.178		0.178
123.90	126.50	VEI;;Qz;;40°;; <b>Vein Quartz 40°</b> 20% of white, 1-3cm quartz veins at 40 TCA.	124.50	126.00	208296	1.50	0.897		0.897
			126.00	127.70	208297	1.70	0.100		0.100
			127.70	129.00	208298	1.30	0.026		0.026
			129.00	130.50	208299	1.50	0.022		0.022
			130.50	132.00	208301	1.50	0.071		0.071
			132.00	133.50	208302	1.50	<0.005		0.001
			133.50	135.00	208303	1.50	0.016		0.016
			135.00	136.50	208304	1.50	0.012		0.012
			136.50	138.00	208305	1.50	<0.005		0.001
			138.00	139.50	208306	1.50	<0.005		0.001
			139.50	141.00	208307	1.50	<0.005		0.001
			141.00	142.50	208308	1.50	0.013		0.013
			142.50	144.00	208309	1.50	<0.005		0.001
			144.00	145.50	208310	1.50	<0.005		0.001
			145.50	147.00	208311	1.50	0.006		0.006
147.00	148.50	208312	1.50	0.076		0.076			
148.50	150.00	208313	1.50	0.038		0.038			
150.00	151.50	208314	1.50	0.035		0.035			
151.15	151.25	VEI;4;QzCl;;20°;Py01; <b>Vein 4 Quartz Chlorite 20° Pyrite01%</b> A 4cm quartz-black chlorite vein at 20 TCA. 1% very fine pyrite.	151.50	153.50	208316	2.00	0.073		0.073
153.50	166.00	SY; MNZD; POR							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
153.50	166.00	<p><b>Syenite 40°; Mineralized; Porphyric</b> RS ZONE. Sharp contacts at 40 TCA. Mineralized, very hard grey-purple to greenish porphyry syenite with 15% of white to greenish (sericitized ?), 3-10mm chubby, prismatic or anhedral feldspar phenocrystals in a mineralized (1 to 4% of very fine pyrite), strongly silicified, sericitized, carbonatized and probably albitized aphanitic matrix. Cross-cut by 5% of at least two different generations of carbonate millimetric veinlets at 20 degrees and 60 degrees (the second cutting the first one).</p> <p>Sil; Ser; Car; Alb <b>Silicification; Sericitisation; Carbonatisation; Albitisation</b></p>							
153.50	166.00	<p>BRE <b>Breccia</b> Locally brecciated.</p>							
153.50	166.00	<p>Py02 <b>Pyrite 02%</b> RS zone with 1 to 4% of very fine, disseminated pyrite.</p>	153.50	154.50	208317	1.00	3.960	3.86	3.860
			154.50	156.00	208318	1.50	2.820		2.820
			156.00	157.50	208319	1.50	2.940		2.940
			157.50	159.00	208321	1.50	2.100		2.100
			159.00	160.50	208322	1.50	1.675		1.675
			160.50	162.00	208323	1.50	2.220		2.220
			162.00	163.50	208324	1.50	2.530		2.530
			163.50	165.00	208325	1.50	1.670		1.670
			165.00	166.00	208326	1.00	0.314		0.314
166.00	189.00	<p>GA <b>Gabbro 40°</b> Sharp upper contact at 40 TCA. Green, strongly chloritized, well laminated in the first 14m then increasingly massive, fine grained, magnetic mafic intrusive. Locally 1% of fine, smaller than 1mm long yellowish leucoxene. Less than 1% of millimetric white calcite veinlets parallel to the lamination.</p> <p>END OF HOLE AT 189m.</p>							
166.00	189.00	<p>Chl; Car <b>Chloritisation; Carbonatisation</b> Pervasive chloritization. Locally carbonatized.</p>	166.00	168.00	208327	2.00	0.148		0.148
			168.00	169.50	208328	1.50	1.115		1.115
166.00	180.00	FOL							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
Foliation 40°								
168.20	168.50	Py02	169.50	171.00	208329	1.50	0.816	0.816
		<b>Pyrite 02%</b>	171.00	172.50	208330	1.50	2.110	2.110
		Mineralized zone at 55 TCA.	172.50	174.00	208331	1.50	0.791	0.791
			174.00	175.50	208332	1.50	0.061	0.061
			175.50	177.00	208333	1.50	<0.005	0.001
			177.00	178.50	208334	1.50	<0.005	0.001
			178.50	180.00	208336	1.50	0.007	0.007
			180.00	181.50	208337	1.50	<0.005	0.001
			181.50	183.00	208338	1.50	<0.005	0.001
			183.00	184.50	208339	1.50	<0.005	0.001
			184.50	186.00	208341	1.50	<0.005	0.001
			186.00	187.50	208342	1.50	<0.005	0.001
			187.50	189.00	208343	1.50	<0.005	0.001
189.00	Fin du sondage							
	Nombre d'échantillons : 122							
	Nombre d'échantillons QAQC : 14							
	Longueur totale échantillonnée : 183.50							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
16.50	16.50	208215	O61d	0.00	4.870	4.760
22.20	22.20	208220	m	0.00	<0.005	0.001
43.50	43.50	208235	O53Pb	0.00	0.630	0.630
49.50	49.50	208240	m	0.00	0.005	0.005
70.50	70.50	208255	O15Pa	0.00	1.010	1.010
76.50	76.50	208260	m	0.00	<0.005	0.001
97.50	97.50	208275	O6Pc	0.00	1.605	1.605
103.50	103.50	208280	m	0.00	<0.005	0.001
124.50	124.50	208295	O54Pa	0.00	3.040	2.960
130.50	130.50	208300	m	0.00	<0.005	0.001
151.50	151.50	208315	O50Pb	0.00	0.861	0.861
157.50	157.50	208320	m	0.00	0.008	0.008
178.50	178.50	208335	O61d	0.00	5.010	4.900
184.50	184.50	208340	m	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-72	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau : surface
	Rang :	Place de travail : Beattie Mine site
Foré par : Foramex	Lot :	
Décrit par : C. Gagnier	Du : 2009-10-24	Date de description : 2009-11-03
	Au : 2009-10-26	

Collet

Azimut : 147.98°  
 Plongée : -42.00°  
 Longueur : 156.00 m

UTM

Est	630 800.5
Nord	5 374 383.8
Élévation	313.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	4.00	147.64°	-43.33°	Non
Reflex	8.00	147.76°	-43.05°	Non
Reflex	12.00	147.88°	-43.51°	Non
Reflex	16.00	148.09°	-43.10°	Non
Reflex	20.00	148.21°	-43.08°	Non
Reflex	24.00	148.37°	-43.57°	Non
Reflex	28.00	148.51°	-43.34°	Non
Reflex	32.00	148.77°	-43.05°	Non
Reflex	36.00	148.99°	-43.27°	Non
Reflex	40.00	149.09°	-43.60°	Non
Reflex	44.00	149.35°	-43.35°	Non
Reflex	48.00	149.51°	-43.02°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	52.00	149.67°	-43.35°	Non
Reflex	56.00	149.71°	-43.60°	Non
Reflex	60.00	149.79°	-43.14°	Non
Reflex	64.00	149.92°	-43.14°	Non
Reflex	68.00	149.96°	-43.57°	Non
Reflex	72.00	150.06°	-43.52°	Non
Reflex	76.00	150.28°	-43.12°	Non
Reflex	80.00	150.36°	-43.27°	Non
Reflex	84.00	150.54°	-43.58°	Non
Reflex	88.00	150.73°	-43.16°	Non
Reflex	92.00	150.84°	-43.26°	Non
Reflex	96.00	151.16°	-43.59°	Non

Description

GPS Datum NAD83, UTM Zone 17.

A multi-shot test has been taken. No single-shot tests were taken.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	100.00	151.35°	-43.38°	Non					
Reflex	104.00	151.44°	-43.08°	Non					
Reflex	108.00	151.56°	-43.29°	Non					
Reflex	112.00	151.71°	-43.50°	Non					
Reflex	116.00	151.88°	-43.05°	Non					
Reflex	120.00	152.13°	-42.96°	Non					
Reflex	124.00	152.30°	-43.46°	Non					
Reflex	128.00	152.38°	-43.27°	Non					
Reflex	132.00	152.67°	-42.88°	Non					
Reflex	136.00	152.79°	-43.28°	Non					
Reflex	140.00	152.97°	-43.37°	Non					
Reflex	144.00	153.10°	-42.92°	Non					
Reflex	148.00	153.14°	-42.72°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.50	MT <b>Casing</b>						
1.50	10.00	SY; POR <b>Syenite 50°; Porphyric</b> Red to greenish, locally porphyric with 10% of anhedral, chloritized, 3mm to 6mm feldspar phenocrysts. In chloritized (green) portions, well foliated at 50 TCA. Strongly weathered (brown, hematized broken core). Not magnetic. In the last meter, the unit is cross-cut by 1-2% of thin, white carbonate veinlets at 30 TCA. Sharp lower contact at 80 TCA.						
1.50	10.00	Chl; Ser; Wea <b>Chloritisation; Sericitisation; Weathering (Incl. Saproplitic alter.)</b>	1.50	3.75	208344	2.25	<0.005	0.001
			3.75	6.00	208345	2.25	0.005	0.005
4.00	6.40	FOL <b>Foliation 50°</b> Foliation made by chlorite laminas.						
5.80	6.00	VEI;2;QzCbCl;40°;00; <b>Vein 2 Quartz Carbonate Chlorite 40° 00%</b> 40% of strongly hematized quartz-carbonate-chlorite veins at 40 TCA. Not mineralized.	6.00	7.50	208346	1.50	0.005	0.005
			7.50	8.75	208347	1.25	0.067	0.067
			8.75	10.00	208348	1.25	0.136	0.136
10.00	90.00	SY; MNZD; POR <b>Syenite; Mineralized; Porphyric</b> RW ZONE. Sharp upper contact at 80 TCA. Grey to greenish, mineralized (very variable: from 0% to 5% of fine pyrite), brecciated, porphyric with locally up to 15% of chloritized-sericitized anhedral, 0.5 to 2cm feldspar phenocrystals. Strongly silicified, sericitized, carbonated (2% of web-like, thin, millimetric dolomite-ankerite veinlets) and locally albitized (purplish color). Locally weathered (hematized) and fractured. Cross-cutted by 2% of 1-10mm quartz-carbonate spider net like veinlets. Gradational lower contact over 20cm.	10.00	11.80	208349	1.80	2.640	2.640
			11.80	13.50	208350	1.70	4.460	4.930
							4.93	
10.00	49.20	Sil; Ser; Car; Alb; Wea <b>Silicification; Sericitisation; Carbonatisation; Albitisation; Weathering (Incl. Saproplitic alter.)</b> Strong silicification, sericitization, carbonatization. Locally albitized and weathered (brown hematite along fractured planes).						
10.00	13.00	BRE <b>Breccia</b>						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
10.00	49.20	Locally brecciated. Py02 <b>Pyrite 02%</b> RW ZONE: Very variable mineralization: from 0 to 5% of very fine pyrite.							
13.00	21.00	BC; BRE <b>Broken core ; Breccia</b> 10% of weathered (hematized) broken core. Locally brecciated.	13.50	15.00	208351	1.50	5.240	5.07	5.070
			15.00	16.50	208352	1.50	6.620	6.48	6.480
			16.50	18.00	208353	1.50	1.240		1.240
			18.00	19.50	208354	1.50	2.880		2.880
			19.50	21.00	208356	1.50	3.320	3.39	3.390
21.00	49.20	BRE <b>Breccia</b> Locally brecciated.	21.00	22.50	208357	1.50	1.380		1.380
			22.50	24.00	208358	1.50	0.492		0.492
			24.00	25.50	208359	1.50	0.171		0.171
			25.50	27.00	208361	1.50	0.090		0.090
			27.00	28.50	208362	1.50	0.276		0.276
			28.50	30.00	208363	1.50	0.207		0.207
			30.00	31.50	208364	1.50	0.952		0.952
			31.50	33.00	208365	1.50	0.728		0.728
			33.00	34.50	208366	1.50	1.625		1.625
			34.50	36.00	208367	1.50	0.267		0.267
			36.00	37.50	208368	1.50	6.420	6.73	6.730
			37.50	39.00	208369	1.50	2.830		2.830
			39.00	40.50	208370	1.50	1.650		1.650
			40.50	42.00	208371	1.50	1.595		1.595
			42.00	43.50	208372	1.50	4.960	4.87	4.870
			43.50	45.00	208373	1.50	3.570	3.64	3.640
			45.00	46.50	208374	1.50	5.190	5.24	5.240
			46.50	48.00	208376	1.50	5.910	5.73	5.730
			48.00	49.50	208377	1.50	6.830	6.43	6.430
49.20	55.90	LT POR; MNZD <b>Lath porphyry; Mineralized</b> Sharp upper contact at 50 TCA. Grey, silicified and sericitized lath porphyry with 40% of 3mm-12mm long white feldspar phenocrystals oriented at 25 TCA in a mineralized very fine grain matrix (0.5 to 2% fine pyrite). 3% of generally flat (10 to up							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
49.20	95.00	to 40 TCA) carbonate-quartz veinlets (at least 2 generations involved). Gradational lower contact over 10cm.						
		Sil; Ser	49.50	51.00	208378	1.50	1.440	1.440
		<b>Silicification; Sericitisation</b>	51.00	52.50	208379	1.50	0.893	0.893
			52.50	54.00	208381	1.50	1.055	1.055
			54.00	55.50	208382	1.50	1.200	1.200
			55.50	57.00	208383	1.50	0.750	0.750
49.20	55.90	LATH <b>Lath orientation 25°</b>						
49.20	55.90	Py01 <b>Pyrite 01%</b> Mineralized lath porphyry: 0.5 to 2% of fine pyrite.						
49.20	55.90	VEI;0.5;CbQz;;10°;00; <b>Vein 0.5 Carbonate Quartz 10° 00%</b> 3% of generally flat (10 TCA to rarely up to 40 TCA) carbonate-quartz 3-10mm veinlets (at least 2 generations involved).						
55.90	90.00	BRE <b>Breccia</b> Locally brecciated.						
55.90	95.00	Py01	57.00	58.50	208384	1.50	0.091	0.091
		<b>Pyrite 01%</b> Very variable mineralization: 0.1 to 5% of fine pyrite.	58.50	60.00	208385	1.50	0.177	0.177
59.10	61.50	VEI;;CbQz;;50°;00;	60.00	61.50	208386	1.50	0.040	0.040
		<b>Vein Carbonate Quartz 50° 00%</b> 10% of 2-20mm (average: 3mm) white carbonate and colorless quartz tension veinlets at 50 TCA.	61.50	63.00	208387	1.50	0.010	0.010
			63.00	64.70	208388	1.70	0.008	0.008
			64.70	66.00	208389	1.30	0.012	0.012
			66.00	67.50	208390	1.50	0.283	0.283
			67.50	69.00	208391	1.50	0.303	0.303
			69.00	70.50	208392	1.50	2.590	2.590
	70.50	72.00	208393	1.50	1.210	1.210		
	72.00	73.50	208394	1.50	1.340	1.340		
	73.50	75.00	208396	1.50	1.045	1.045		
	75.00	76.50	208397	1.50	0.597	0.597		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
90.00	119.70	ANJ; APH <b>Andesite 50°; Aphanitic</b> Gradational upper contact over 20cm. Generally yellow (sericitized), aphanitic, bleached volcanic unit showing locally shattered glass cooling fractures with 10% of greyish to beige, silicified and possibly albitized, brecciated, mineralized (pyrite and arsenopyrite) portions. Foliation at 50 TCA. Gradational lower contact over 30cm.	76.50	78.00	208398	1.50	0.434		0.434
			78.00	79.50	208399	1.50	1.290		1.290
			79.50	81.00	208401	1.50	1.020		1.020
			81.00	82.50	208402	1.50	0.981		0.981
			82.50	84.00	208403	1.50	0.303		0.303
			84.00	85.50	208404	1.50	0.357		0.357
			85.50	87.00	208405	1.50	1.900		1.900
			87.00	88.50	208406	1.50	0.559		0.559
			88.50	90.00	208407	1.50	0.227		0.227
90.00	119.70	FOL <b>Foliation 50°</b>	90.00	91.50	208408	1.50	6.920	7.54	7.540
			91.50	93.00	208409	1.50	8.850	8.77	8.770
			93.00	94.50	208410	1.50	8.790	8.97	8.970
			94.50	96.00	208411	1.50	1.040		1.040
95.00	119.70	Ser; Sil <b>Sericitisation; Silicification</b> General yellowish, strong sericitization with 10% of grey to beige, mineralized, silicified, possibly albitized, brecciated zones.	96.00	97.50	208412	1.50	0.714		0.714
			97.50	99.00	208413	1.50	1.440		1.440
			99.00	100.50	208414	1.50	0.020		0.020
			100.50	102.00	208416	1.50	0.840		0.840
			102.00	103.50	208417	1.50	0.244		0.244
			103.50	105.00	208418	1.50	0.799		0.799
			105.00	106.50	208419	1.50	3.070	3.12	3.120
			106.50	108.00	208421	1.50	2.110		2.110
			108.00	109.50	208422	1.50	1.165		1.165
			109.50	111.00	208423	1.50	0.013		0.013
			111.00	112.50	208424	1.50	0.322		0.322
112.50	114.00	208425	1.50	0.046		0.046			
114.00	115.50	208426	1.50	0.049		0.049			
115.50	117.00	208427	1.50	0.032		0.032			

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			117.00	118.50	208428	1.50		0.011
			118.50	119.70	208429	1.20		0.011
95.00	107.10	Py0.5; As0.2 <b>Pyrite 0.5%; Arsenopyrite 0.2%</b> Mineralization associated to a 10% of greyish, aphanitic, silicified, brecciated portion.						
119.70	156.00	GA; MAS <b>Gabbro 60°; Massive rock</b> Gradational upper contact over 30cm. Dark green, strongly chloritized medium size grain gabbro (average: 1mm) made mainly of dark green mafic, anhedral minerals and greyish plagioclase . 1% of light yellow, less than 1mm leucoxene shards. Weakly foliated at 60 TCA. Not magnetic. Less than 1% of 1-3mm white calcite veinlets parallel to the foliation. END OF HOLE AT 156m.						
119.70	156.00	Chl <b>Chloritisation</b> Strong pervasive chloritization.						
119.70	156.00	FOL <b>Foliation 60°</b> Weak foliation.	119.70	121.50	208430	1.80		0.009
			121.50	123.30	208431	1.80		0.010
			123.30	124.50	208432	1.20		<0.005
			124.50	126.00	208433	1.50		0.007
			126.00	127.50	208434	1.50		0.393
			127.50	129.00	208436	1.50		0.046
			129.00	130.50	208437	1.50		0.008
			130.50	132.00	208438	1.50		<0.005
			132.00	133.50	208439	1.50		<0.005
			133.50	135.00	208441	1.50		0.005
			135.00	136.50	208442	1.50		<0.005
			136.50	138.00	208443	1.50		0.005
			138.00	139.50	208444	1.50		0.022
			139.50	141.00	208445	1.50		0.006
			141.00	142.50	208446	1.50		<0.005
			142.50	144.00	208447	1.50		0.007
			144.00	145.50	208448	1.50		0.006
			145.50	147.00	208449	1.50		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.00	148.50	208450	1.50	0.439		0.439
	148.50	150.00	208451	1.50	0.006		0.006
	150.00	151.50	208452	1.50	0.005		0.005
	151.50	153.00	208453	1.50	0.005		0.005
	153.00	154.50	208454	1.50	<0.005		0.001
	154.50	156.00	208456	1.50	0.006		0.006
156.00	Fin du sondage Nombre d'échantillons : 102 Nombre d'échantillons QAQC : 11 Longueur totale échantillonnée : 154.50						

## Corporation Minière Osisko Div. Exploration

## QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
19.50	19.50	208355	O53Pb	0.00	0.630	0.630
25.50	25.50	208360	m	0.00	0.005	0.005
46.50	46.50	208375	O15Pa	0.00	1.005	1.005
52.50	52.50	208380	m	0.00	0.021	0.021
73.50	73.50	208395	O6Pc	0.00	1.605	1.605
79.50	79.50	208400	m	0.00	0.005	0.005
100.50	100.50	208415	O50Pb	0.00	0.823	0.823
106.50	106.50	208420	m	0.00	0.006	0.006
127.50	127.50	208435	O61d	0.00	4.750	4.730
133.50	133.50	208440	m	0.00	<0.005	0.001
154.50	154.50	208455	O53Pb	0.00	0.588	0.588

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-73

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface hole

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C. Gagnier

Du : 2009-10-26

Date de description : 2009-11-08

Au : 2009-10-28

Collet

Azimut : 153.50°  
 Plongée : -54.10°  
 Longueur : 195.00 m

UTM

Est	630 782.6
Nord	5 374 412.6
Élévation	313.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	4.00	153.69°	-52.89°	Non
Reflex	8.00	153.39°	-52.30°	Non
Reflex	12.00	153.31°	-52.62°	Non
Reflex	16.00	153.48°	-52.59°	Non
Reflex	20.00	153.56°	-52.19°	Non
Reflex	24.00	153.64°	-52.19°	Non
Reflex	28.00	153.76°	-52.61°	Non
Reflex	32.00	153.86°	-52.78°	Non
Reflex	36.00	153.96°	-51.97°	Non
Reflex	40.00	153.98°	-52.51°	Non
Reflex	44.00	154.15°	-52.53°	Non
Reflex	48.00	154.22°	-51.97°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	52.00	154.33°	-52.17°	Non
Reflex	56.00	154.53°	-52.43°	Non
Reflex	60.00	154.65°	-51.99°	Non
Reflex	64.00	154.74°	-52.12°	Non
Reflex	68.00	154.95°	-52.50°	Non
Reflex	72.00	155.17°	-52.09°	Non
Reflex	76.00	155.35°	-51.91°	Non
Reflex	80.00	155.54°	-52.44°	Non
Reflex	84.00	155.61°	-52.36°	Non
Reflex	88.00	155.61°	-51.97°	Non
Reflex	92.00	155.72°	-52.20°	Non
Reflex	96.00	155.84°	-52.45°	Non

Description

GPS Datum NAD83, UTM Zone 17.

The single-shot tests were corrected for magnetic declination (12.5 degrees to the west). A Devico multi-shot was also taken. Hole surveyed (Nov 2009) by Descarreaux.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviaton

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	100.00	155.87°	-52.06°	Non					
Reflex	104.00	155.93°	-51.81°	Non					
Reflex	108.00	156.15°	-52.32°	Non					
Reflex	112.00	156.26°	-52.16°	Non					
Reflex	116.00	156.33°	-51.10°	Non					
Reflex	120.00	156.45°	-52.16°	Non					
Reflex	124.00	156.58°	-52.33°	Non					
Reflex	128.00	156.69°	-51.91°	Non					
Reflex	132.00	156.79°	-51.90°	Non					
Reflex	136.00	156.83°	-52.32°	Non					
Reflex	140.00	156.81°	-52.07°	Non					
Reflex	144.00	156.82°	-51.68°	Non					
Reflex	148.00	157.08°	-51.96°	Non					
Reflex	152.00	157.25°	-52.22°	Non					
Reflex	156.00	157.34°	-51.72°	Non					
Reflex	160.00	157.51°	-51.92°	Non					
Reflex	164.00	157.62°	-52.30°	Non					
Reflex	168.00	157.78°	-51.86°	Non					
Reflex	172.00	158.01°	-51.77°	Non					
Reflex	176.00	158.13°	-52.10°	Non					
Reflex	180.00	158.16°	-52.11°	Non					
Reflex	184.00	158.28°	-51.58°	Non					
Reflex	188.00	158.33°	-51.48°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	8.00	MT <b>overburden</b>						
8.00	148.00	SY; MAS <b>Syenite; Massive rock</b> Casing at 9m. Red with green chlorite shards, mottled, massive, not magnetic syenite with less than 10% anhedral, 2-10mm white feldspar phenocrystals. Cross-cut by 1% of millimetric white feldspar-quartz and sometimes chlorite veinlets generally at 60 TCA. Locally brecciated. Lower contact by a 5cm flat aplite vein (pink feldspar and colorless quartz).	8.00	9.20	208457	1.20	0.050	0.050
			9.20	10.50	208458	1.30	0.017	0.017
			10.50	12.00	208459	1.50	0.272	0.272
			12.00	13.50	208461	1.50	0.163	0.163
8.00	17.00	Wea; Chl <b>Weathering (Incl. Saprolitic alter.); Chloritisation</b>						
8.00	13.40	FRC <b>Fractured</b> RQD=20%						
13.40	15.00	FOL <b>Foliation 50°</b> Foliation in a strongly chloritized, apple-green zone.	13.50	15.00	208462	1.50	0.029	0.029
			15.00	16.50	208463	1.50	0.115	0.115
			16.50	18.00	208464	1.50	0.188	0.188
			18.00	19.50	208465	1.50	0.007	0.007
			19.50	21.00	208466	1.50	0.006	0.006
			21.00	22.50	208467	1.50	0.014	0.014
21.50	26.50	Chl <b>Chloritisation</b> Strong chloritization on both walls of centimetric quartz veins at 80 TCA.						
22.00	26.00	FOL <b>Foliation 50°</b> Strongly chloritized, apple-green zone foliated at 50 TCA.	22.50	24.00	208468	1.50	0.251	0.251
22.60	26.00	VEI;1;;;50°;00; <b>Vein 1 50° 00%</b> 5% of 1cm white quartz veins at 50 TCA.	24.00	25.50	208469	1.50	0.013	0.013
			25.50	27.00	208470	1.50	0.036	0.036
			27.00	28.50	208471	1.50	0.013	0.013
			28.50	30.00	208472	1.50	0.007	0.007
			30.00	31.50	208473	1.50	0.093	0.093
			31.50	33.00	208474	1.50	<0.005	0.001
			33.00	34.50	208476	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			34.50	36.00	208477	1.50	<0.005		0.001
			36.00	37.50	208478	1.50	<0.005		0.001
			37.50	39.00	208479	1.50	0.010		0.010
			39.00	40.50	208481	1.50	0.037		0.037
			40.50	42.00	208482	1.50	<0.005		0.001
			42.00	43.50	208483	1.50	0.014		0.014
			43.50	45.00	208484	1.50	0.218		0.218
44.00	51.00	VEI;QzFp;;50°;; <b>Vein Quartz Feldspath (alkaline) 50°</b> 5% of centimetric quartz-feldspar veins at 50 TCA.	45.00	46.50	208485	1.50	<0.005		0.001
			46.50	48.00	208486	1.50	0.029		0.029
47.50	53.00	Ser <b>Sericitisation</b> Gradational contacts over 20cm. Apple green sericitization associated to 2% of quartz-feldspar veinlets.							
48.00	53.00	Py0.5 <b>Pyrite 0.5%</b> Locally up to 1% of euhedral pyrite in a sericitized zone.	48.00	49.50	208487	1.50	0.064		0.064
			49.50	51.00	208488	1.50	0.290		0.290
			51.00	52.50	208489	1.50	0.008		0.008
			52.50	54.00	208490	1.50	0.013		0.013
54.00	55.00	Wea <b>Weathering (Incl. Saprolitic alter.)</b> Hematized flat fractures.	54.00	55.50	208491	1.50	<0.005		0.001
			55.50	57.00	208492	1.50	<0.005		0.001
			57.00	58.50	208493	1.50	0.006		0.006
			58.50	60.00	208494	1.50	0.006		0.006
			60.00	61.50	208496	1.50	0.105		0.105
			61.50	63.00	208497	1.50	0.452		0.452
			63.00	64.50	208498	1.50	0.019		0.019
			64.50	66.00	208499	1.50	0.046		0.046
			66.00	67.50	212501	1.50	<0.005		0.001
			67.50	69.00	212502	1.50	0.006		0.006
			69.00	70.50	212503	1.50	<0.005		0.001
			70.50	72.00	212504	1.50	<0.005		0.001
			72.00	73.50	212505	1.50	0.019		0.019
			73.50	75.00	212506	1.50	<0.005		0.001
			75.00	76.50	212507	1.50	<0.005		0.001
			76.50	78.00	212508	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			78.00	79.50	212509	1.50		0.029		0.029
			79.50	81.00	212510	1.50		<0.005		0.001
			81.00	82.50	212511	1.50		0.008		0.008
			82.50	84.00	212512	1.50		0.024		0.024
			84.00	85.50	212513	1.50		0.193		0.193
			85.50	87.00	212514	1.50		0.007		0.007
			87.00	88.50	212516	1.50		<0.005		0.001
			88.50	90.00	212517	1.50		<0.005		0.001
			90.00	91.50	212518	1.50		0.123		0.123
			91.50	93.00	212519	1.50		<0.005		0.001
			93.00	94.50	212521	1.50		<0.005		0.001
			94.50	96.00	212522	1.50		<0.005		0.001
			96.00	97.50	212523	1.50		<0.005		0.001
97.00	103.20	I2D LT POR <b>Syenite Lath Porphyry Intrusive</b> Sharp contacts at 50 TCA. Red to greenish lath porphyry syenite with 40% of white to reddish (hematized), 1-2cm long K-feldspar phenocrystals. Not mineralized matrix.								
97.00	103.70	LATH <b>oriented phenocrysts 50°</b> K-feldspar lath phenocrysts elongated at 50 TCA.								
97.50	110.30	Chl <b>Chloritisation</b> Moderate pervasive chloritization.	97.50	99.00	212524	1.50		0.011		0.011
			99.00	100.50	212525	1.50		0.006		0.006
			100.50	102.00	212526	1.50		0.202		0.202
			102.00	103.50	212527	1.50		0.030		0.030
			103.50	105.00	212528	1.50		<0.005		0.001
			105.00	106.50	212529	1.50		0.012		0.012
			106.50	108.00	212530	1.50		0.074		0.074
			108.00	109.50	212531	1.50		0.341		0.341
			109.50	111.00	212532	1.50		0.144		0.144
			111.00	112.50	212533	1.50		<0.005		0.001
			112.50	114.00	212534	1.50		<0.005		0.001
			114.00	115.50	212536	1.50		<0.005		0.001
			115.50	117.00	212537	1.50		<0.005		0.001
			117.00	118.50	212538	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
129.00	133.00	Chi; Wea <b>Chloritisation; Weathering (Incl. Saprolitic alter.)</b> Chloritization and hematization on both walls of 1-2cm quartz veins.	118.50	120.00	212539	1.50	<0.005	3.99	0.001
			120.00	121.50	212541	1.50	<0.005		0.001
			121.50	123.00	212542	1.50	<0.005		0.001
			123.00	124.50	212543	1.50	0.050		0.050
			124.50	126.00	212544	1.50	<0.005		0.001
			126.00	127.50	212545	1.50	0.008		0.008
			127.50	129.00	212546	1.50	0.007		0.007
			129.00	130.50	212547	1.50	0.105		0.105
			130.50	132.00	212548	1.50	0.020		0.020
			132.00	133.50	212549	1.50	0.058		0.058
			133.50	135.00	212550	1.50	0.012		0.012
			135.00	136.50	212551	1.50	0.005		0.005
			136.50	138.00	212552	1.50	0.008		0.008
			138.00	139.50	212553	1.50	0.219		0.219
			139.50	141.00	212554	1.50	0.012		0.012
			141.00	142.50	212556	1.50	0.027		0.027
			142.50	144.00	212557	1.50	<0.005		0.001
144.00	145.50	212558	1.50	0.007	0.007				
145.50	147.00	212559	1.50	0.096	0.096				
147.00	148.00	212561	1.00	0.038	0.038				
129.00	130.60	VEI;;QzCb;;40°; <b>Vein Quartz Carbonate 40°</b> 5% of 1-2cm quartz-carbonate smoky or white veins at 40 or 80 TCA.							
147.70	148.00	VEI;5;FpQz;;00°;00; <b>Vein 5 Feldspath (alkaline) Quartz 00° 00%</b> A 5cm flat aplite vein (pink K-feldspar and colorless quartz) at the upper contact of a mineralized zone.							
148.00	170.90	SY; MNZ <b>Syenite; Mineralized</b> Veined upper contact: 5cm aplite flat pink feldspar-colorless quartz vein. Pink to grey porphyry syenite, locally silicified and locally mineralized with 0.5 to 10% fine pyrite (average: 2%). Locally cross-cut by up to 3% of white, millimetric feldspar veinlets at 60 TCA. Not magnetic. Sharp lower contact at 60 TCA.	148.00	150.00	212562	2.00	0.561	3.99	0.561
			150.00	151.50	212563	1.50	2.300		2.300
			151.50	153.00	212564	1.50	4.060		3.990
			153.00	154.50	212565	1.50	0.792		0.792
			154.50	156.00	212566	1.50	0.466		0.466
156.00	157.50	212567	1.50	0.546	0.546				

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			157.50	159.00	212568	1.50	0.810		0.810
			159.00	160.50	212569	1.50	0.102		0.102
			160.50	162.00	212570	1.50	0.412		0.412
			162.00	163.50	212571	1.50	0.077		0.077
			163.50	165.00	212572	1.50	0.217		0.217
148.00	157.10	Py03 <b>Pyrite 03%</b> 0.5 to 10% fine pyrite.							
164.20	170.40	Sil; Car <b>Silicification; Carbonatisation</b> Locally altered (silicification, carbonatized) mineralized zone, taking then a greyish color.							
164.20	170.40	Py01 <b>Pyrite 01%</b> Grey to redish porphyry syenite, locally silicified and carbonatized, mineralized with 0.5 to 2% of fine pyrite.	165.00	166.50	212573	1.50	1.345		1.345
			166.50	168.00	212574	1.50	0.596		0.596
			168.00	169.50	212576	1.50	0.271		0.271
			169.50	171.00	212577	1.50	0.233		0.233
170.90	195.00	GA <b>Gabbro</b> Sharp upper contact at 60 TCA. Dark green, strongly chloritized, carbonatized dolerite (very fine grain gabbro) or volcanite (andesite). Not magnetic. 1% of yellowish, smaller than 1mm leucoxene shards. The first 10 m shows a foliation at 40 TCA. This foliation disappears progressively as we go away of the upper contact. The unit becomes progressively massive and the grain size increases to be 0.25 to 0.5mm in average at 192m.  END OF HOLE AT 195m.							
170.90	195.00	Chl; Car <b>Chloritisation; Carbonatisation</b> Strong chloritization and carbonatization.	171.00	172.50	212578	1.50	1.095		1.095
			172.50	174.00	212579	1.50	2.360		2.360
			174.00	175.50	212581	1.50	0.150		0.150
			175.50	177.00	212582	1.50	0.016		0.016
			177.00	178.50	212583	1.50	<0.005		0.001
			178.50	180.00	212584	1.50	<0.005		0.001
			180.00	181.50	212585	1.50	<0.005		0.001
			181.50	183.00	212586	1.50	<0.005		0.001
			183.00	184.50	212587	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
170.90      181.70      FOL Foliation 40°	184.50	186.00	212588	1.50	<0.005		0.001
	186.00	187.50	212589	1.50	<0.005		0.001
	187.50	189.00	212590	1.50	<0.005		0.001
	189.00	190.50	212591	1.50	<0.005		0.001
	190.50	192.00	212592	1.50	<0.005		0.001
	192.00	193.50	212593	1.50	0.006		0.006
	193.50	195.00	212594	1.50	<0.005		0.001
	195.00	Fin du sondage Nombre d'échantillons : 125 Nombre d'échantillons QAQC : 14 Longueur totale échantillonnée : 187.00					

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.00	12.00	208460	m	0.00	<0.005	0.001
33.00	33.00	208475	O15Pa	0.00	1.020	1.020
39.00	39.00	208480	m	0.00	<0.005	0.001
60.00	60.00	208495	O6Pc	0.00	1.665	1.665
66.00	66.00	208500	m	0.00	<0.005	0.001
87.00	87.00	212515	O54Pa	0.00	3.020	3.050
93.00	93.00	212520	m	0.00	<0.005	0.001
114.00	114.00	212535	O50Pb	0.00	0.866	0.866
120.00	120.00	212540	m	0.00	<0.005	0.001
141.00	141.00	212555	O6Pc	0.00	1.500	1.500
147.00	147.00	212560	m	0.00	<0.005	0.001
168.00	168.00	212575	O54Pa	0.00	2.940	2.940
174.00	174.00	212580	m	0.00	<0.005	0.001
194.99	195.00	212595	O50Pb	0.01	0.848	0.848



## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-74

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : Surface

Rang :

Place de travail : Beattie Mine Site

Foré par : Foramex

Lot :

Décrit par : Carl Corriveau

Du : 2009-10-30

Date de description : 2009-11-04

Au : 2009-11-01

Collet

UTM

Azimut : 166.69°

Plongée : -52.80°

Longueur : 201.00 m

Est 630 804.9

Nord 5 374 420.8

Élévation 313.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	166.70°	-53.78°	Non
Reflex	2.00	166.78°	-53.84°	Non
Reflex	5.00	166.89°	-53.70°	Non
Reflex	8.00	166.96°	-53.80°	Non
Reflex	11.00	167.06°	-54.14°	Non
Reflex	14.00	167.19°	-54.07°	Non
Reflex	17.00	167.34°	-53.92°	Non
Reflex	20.00	167.42°	-53.78°	Non
Reflex	23.00	167.60°	-53.39°	Non
Reflex	26.00	167.71°	-53.51°	Non
Reflex	29.00	167.88°	-53.84°	Non
Reflex	32.00	168.05°	-53.96°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	35.00	168.24°	-53.47°	Non
Reflex	38.00	168.37°	-53.58°	Non
Reflex	41.00	168.51°	-53.98°	Non
Reflex	44.00	168.66°	-53.93°	Non
Reflex	47.00	168.81°	-53.58°	Non
Reflex	50.00	169.07°	-53.38°	Non
Reflex	53.00	169.17°	-53.54°	Non
Reflex	56.00	169.32°	-53.89°	Non
Reflex	59.00	169.46°	-54.04°	Non
Reflex	62.00	169.62°	-53.81°	Non
Reflex	65.00	169.74°	-53.53°	Non
Reflex	68.00	170.01°	-53.52°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Deviflex multishots taken.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	71.00	170.10°	-54.04°	Non	Reflex	170.00	173.54°	-54.12°	Non
Reflex	74.00	170.09°	-53.93°	Non	Reflex	173.00	173.60°	-54.46°	Non
Reflex	77.00	170.20°	-53.98°	Non	Reflex	176.00	173.65°	-54.39°	Non
Reflex	80.00	170.31°	-53.75°	Non	Reflex	179.00	173.80°	-54.28°	Non
Reflex	83.00	170.43°	-54.19°	Non	Reflex	182.00	173.88°	-54.26°	Non
Reflex	86.00	170.52°	-53.91°	Non	Reflex	185.00	174.02°	-54.28°	Non
Reflex	89.00	170.60°	-53.69°	Non					
Reflex	92.00	170.69°	-53.80°	Non					
Reflex	95.00	170.89°	-54.23°	Non					
Reflex	98.00	170.95°	-54.20°	Non					
Reflex	101.00	171.05°	-53.92°	Non					
Reflex	104.00	171.16°	-53.81°	Non					
Reflex	107.00	171.21°	-54.24°	Non					
Reflex	110.00	171.31°	-54.34°	Non					
Reflex	113.00	171.39°	-54.18°	Non					
Reflex	116.00	171.47°	-53.89°	Non					
Reflex	119.00	171.58°	-54.04°	Non					
Reflex	122.00	171.72°	-54.06°	Non					
Reflex	125.00	171.92°	-54.36°	Non					
Reflex	128.00	171.99°	-54.09°	Non					
Reflex	131.00	172.08°	-53.89°	Non					
Reflex	134.00	172.21°	-53.86°	Non					
Reflex	137.00	172.30°	-54.02°	Non					
Reflex	140.00	172.43°	-54.29°	Non					
Reflex	143.00	172.59°	-54.57°	Non					
Reflex	146.00	172.71°	-54.53°	Non					
Reflex	149.00	172.82°	-54.15°	Non					
Reflex	152.00	172.85°	-54.12°	Non					
Reflex	155.00	172.93°	-54.43°	Non					
Reflex	158.00	173.06°	-54.42°	Non					
Reflex	161.00	173.17°	-54.10°	Non					
Reflex	164.00	173.29°	-53.97°	Non					
Reflex	167.00	173.42°	-53.95°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	10.50	MT <b>Casing</b>							
0.00	23.65	BX; BSF <b>Breccia; Breccia Silicified zone</b> Pale red discolored Partially silicified brecciated segments usually 10 to 25 cm (ex; 13.5m 15m 20m) Altered Py boxwerk. Breccia matrix supported, angular 5mm to 20mm syenite clasts.							
0.00	23.65	Sil; Oxy; Ser; Chl <b>Silicification; Oxydation; Sericitisation; Chloritisation</b> Partially silicified segments brecciating locally the host syenite. Iron oxydes Limonite-Hematite in fractures. greenish Sericitized feldspar porphyries and veinlets. Weak albitization associated with Silica veins. Dark green to black chloritized porphyries and veinlets 1%							
0.00	23.65	Py0.5 <b>Pyrite 0.5%</b> Brassy automorph fine to very fine disseminated Py							
10.50	23.65	SY; POR; BSF <b>Syenite; Porphyric; Breccia Silicified zone</b> Redish porphiritic syenite with greenish segments. Pale red discolored Partially silicified and silicified brecciated segments (ex; 13.5m 15m 20m) . Iron oxyde altered fractures and veinlets, Py boxwerk 1-2% in iron oxydized segments. Grey Silica +- Carbonates + - Chl veins. Not mag. 5mm to cm feldspar porphyries rimed and cracked sericitized 5%. Smaller feldspar completely sericitized and/or chloritized. Blackish CHI-HM veinlets 2% cross cutting (ex:19.5m). Slickensides mark by chlorite in fracture. Weak albitization associated with Silica veins	10.50	12.00	202718	1.50	0.012		0.012
			12.00	13.50	202719	1.50	0.011		0.011
			13.50	15.00	202720	1.50	0.010		0.010
			15.00	16.50	202721	1.50	0.021		0.021
			16.50	18.00	202722	1.50	0.015		0.015
			18.00	19.50	202723	1.50	0.043		0.043
			19.50	21.00	202724	1.50	0.014		0.014
			21.00	22.50	202725	1.50	0.012		0.012
			22.50	24.00	202726	1.50	0.016		0.016
23.65	34.50	SY; FOL <b>Syenite; Foliation</b> Gradual upper contact over 10cm, increasing of chloritization (rock pass from red to green). Pale green to medium green chloritized and sericitized foliated syenite. Strong pervasive chloritization and sericitization obliterating partially the primary porphyritic texture along the upper contact. 5% Silica +- albite veins and veinlets crosscutting syenite and partially silicified it. Not magnetic. Very fine beige crystals (could be leucoxene: magnetite Ti alteration). Traces of fine disseminated Py. Chloritized feldspar porphyries. Blackish to Greenish chloritized veinlets 2%. Moderate green sericite veinlets and							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
23.65	34.50	<p>porphyries (form by decomposition of feldspar). Gradual lower contact: rock goes from green to red over 1.5m. 29.9m iron oxyde alteration over 3cm.</p> <p>Chl; Ser; Epi</p> <p><b>Chloritisation; Sericitisation; Epidotisation</b></p> <p>Strong pervasive chloritization and sericitization obliterating partially the primary porphyritic texture along the upper contact. Chloritized feldspar porphyries. Blackish to Greenish chloritized veinlets 2%. Moderate green sericite veinlets and porphyries (form by decomposition of feldspar). Weak epidotized feldspars. 3cm iron oxyde (rusty) at 29.9m.</p>							
23.65	34.50	<p>Py</p> <p><b>Pyrite</b></p> <p>Traces of disseminated automorph brassy Py especially in fracture or associated with silica veins</p>	24.00	25.50	202727	1.50	0.034		0.034
			25.50	27.00	202728	1.50	0.047		0.047
			27.00	28.50	202729	1.50	0.022		0.022
			28.50	30.00	202731	1.50	0.049		0.049
			30.00	31.50	202732	1.50	0.059		0.059
			31.50	33.00	202733	1.50	0.016		0.016
			33.00	34.50	202734	1.50	0.168		0.168
34.50	61.30	<p>SY</p> <p><b>Syenite</b></p> <p>Redish to greenish porphyritic Syenite. 10% subhedral et euhedral feldspars porphyries. 10% white qz-carbonates (white sericite?) veinlets all directions. 3-5% 1 to 3mm Qz-carb cross cutting 60 TCA. Not Mag.</p> <p>43.75-44.20m Qz-Dolomie veins and veinlets of variables sizes all directions. Veinlets of chlorite and sericite all directions. Disseminated brassy Py, automorph, less than 1% visible</p> <p>46.7m-47.45 grey to white Qz (silica)-Dolomie veins brecciating the host rock. Fine chalcopyrite, hématite 1-2%.</p>							
34.50	61.30	<p>Chl; Car</p> <p><b>Chloritisation; Carbonatisation</b></p> <p>Chlorite veinlets and persavise dicolorating syenite to green. Carbonates, usually dolomite in Qz veins. Porphyries partially (rimmed) or totally chloritized.</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
34.50	61.30	FRC <b>Fractured 60°</b> 3-5% 1 to 3mm Qz-carb cross cutting 60 TCA. Not Mag.							
34.50	61.30	Hm; Cp; Py <b>Hematite ; Chalcopyrite ; Pyrite</b> Disseminated automorph Py 0.5%  Mineralized veins, 5mm to 10mm clusters of Hematite-leucoxène +- SF. Also but not consistant in all veins: automorp fine brassy Py traces. Minor Chalcopyrite associate with HM.  43.75-44.20m Qz-Dolomie veins and veinlets of variables sizes all directions. Veinlets of chlorite and sericite all directions. Disseminated brassy Py, automorph, less than 1% visible  46.7m-47.45 grey to white Qz (silica)-Dolomie veins brecciating the host rock. Fine chalcopyrite, hématite 1-2%.							
34.50	61.30	VEI:;;;;; <b>Vein</b> 3-5% 1 to 3mm Qz-carb veins cross cutting 60 TCA. Not Mag.  43.75-44.20m Qz-Dolomie veins and veinlets of variables sizes all directions. Veinlets of chlorite and sericite all directions. Disseminated brassy Py, automorph, less than 1% visible  46.7m-47.45 grey to white Qz (silica)-Dolomie veins brecciating the host rock. Fine chalcopyrite, hématite 1-2%.	34.50	36.00	202735	1.50	0.009		0.009
			36.00	37.50	202736	1.50	0.039		0.039
			37.50	39.00	202737	1.50	<0.005		0.001
			39.00	40.50	202738	1.50	0.006		0.006
			40.50	42.00	202739	1.50	0.063		0.063
			42.00	43.50	202741	1.50	0.018		0.018
			43.50	45.00	202742	1.50	0.011		0.011
			45.00	46.50	202743	1.50	0.025		0.025
			46.50	48.00	202744	1.50	0.851		0.851
			48.00	49.50	202745	1.50	0.029		0.029
			49.50	51.00	202746	1.50	0.005		0.005
			51.00	52.50	202747	1.50	0.005		0.005
			52.50	54.00	202748	1.50	0.012		0.012
			54.00	55.50	202749	1.50	0.018		0.018
			55.50	57.00	202751	1.50	0.010		0.010
			57.00	58.50	202752	1.50	0.005		0.005
			58.50	60.00	202753	1.50	0.005		0.005
			60.00	61.50	202754	1.50	0.009		0.009
61.30	62.40	FOL; POR							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<p><b>Foliation ; Porphyric</b> Moderate green chloritized syenite. Calcite in schisto plans.</p>						
61.30	62.40	<p>Chl; Sil; Car <b>Chloritisation; Silicification; Carbonatisation</b> Pervasive Chl. Partially silicified. carbonates in schisto plans</p>						
61.30	62.40	<p>FOL <b>Foliation 40°</b> 40 degrees TCA Foliation. Slickenside in fracture</p>						
61.30	62.40	<p>Py <b>Pyrite</b> Traces diss brassy Py</p>	61.50	63.00	202755	1.50	0.039	0.039
62.40	102.30	<p>SY <b>Syenite</b> Redish porphyritic Syenite. 5-10% feldspars phenocryst. Fine grain to to aphanitic feldspars matrix. Network ok fine white soft minerals carbonates (could have also sericite or clay) all directions. Thicker White 2mm to cm Qz-Carbonates (dolomite, calcite).. Larger White and translucide 1cm to 5cm silica, dolomite, albites veins. The larger veins brecciating locally the host rock.</p>						
62.40	102.30	<p>Ser; Chl <b>Sericitisation; Chloritisation</b> Network ok fine white soft minerals (could be sericite or clay) all directions. Moderate Chloritized foliated fractures, veins and porphyries</p>						
62.40	102.30	<p>FRC <b>Fractured</b> Oxydized rusty fractures 50TCA Chloritized fractures 75 TCA Slickensides ex:74.2m</p>						
62.40	102.30	<p>Py; Hm <b>Pyrite ; Hematite</b> Locally and unconsistant traces of fine brassy disseminated Py. Size 1mm or less often near or in Silica veins. Traces of Blueish Hematite clusters and veinlets in silica-dol-albite veins also disseminated in syenite.</p>						
62.40	102.30	<p>VEI;::::; <b>Vein</b> 10% Network ok fine white carbonates minerals (could be sericite or chl or clay) all directions spider web texture .</p>	63.00	64.50	202756	1.50	0.005	0.005
			64.50	66.00	202757	1.50	0.100	0.100
			66.00	67.50	202758	1.50	0.042	0.042

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
5% Thicker White 2mm to cm Qz-Carbonates (dolomite, calcite). 2% Larger White and translucent 1cm to 5cm silica, dolomite, albites veins. The larger veins brecciating locally the host rock.			67.50	69.00	202759	1.50	0.007		0.007
			69.00	70.50	202760	1.50	0.013		0.013
			70.50	72.00	202761	1.50	0.027		0.027
			72.00	73.50	202762	1.50	0.005		0.005
			73.50	75.00	202763	1.50	<0.005		0.001
			75.00	76.50	202764	1.50	0.005		0.005
			76.50	78.00	202765	1.50	0.005		0.005
			78.00	79.50	202766	1.50	0.016		0.016
			79.50	81.00	202767	1.50	0.025		0.025
			81.00	82.50	202768	1.50	0.019		0.019
			82.50	84.00	202769	1.50	0.021		0.021
			84.00	85.50	202771	1.50	0.256		0.256
			85.50	87.00	202772	1.50	0.033		0.033
			87.00	88.50	202773	1.50	0.008		0.008
			88.50	90.00	202774	1.50	0.006		0.006
			90.00	91.50	202775	1.50	0.012		0.012
			91.50	93.00	202776	1.50	0.006		0.006
			93.00	94.50	202777	1.50	0.005		0.005
			94.50	96.00	202778	1.50	0.005		0.005
			96.00	97.50	202779	1.50	0.010		0.010
97.50	99.00	202781	1.50	0.006		0.006			
99.00	100.50	202782	1.50	0.006		0.006			
100.50	102.00	202783	1.50	0.005		0.005			
102.00	103.50	202784	1.50	0.010		0.010			
102.30	108.35	PT POR							
<b>Lath porphyry</b> redish to green lath porphyry sienite. Sharp intrusive upper and lower contact. 40-50% of feldspars phenocryst oriented 70 to 80 degrees TCA. Network ok fine white soft carbonates (pervasive)									
102.30	108.35	Chl; Epi							
<b>Chloritisation; Epidotisation</b> 10% greenish veinlets and smalls feldspars Chl altered. 1% Epidotized crystals									
102.30	108.35	Hm							
<b>Hematite</b>									

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		traces to 1% blueish hematite. Clusters in silica veins and disseminated in lat porphyry. Trace of very fine disseminated Py in matrix and silica+carb cm altered segments or veins (ex:107.7m)							
102.30	108.35	VEI;::::; <b>Vein</b> 1% small 1 to 3mm silica + HM veinlets crosscutting (105.7m) 35 degrees TCA	103.50	105.00	202785	1.50	0.011		0.011
			105.00	106.50	202786	1.50	0.014		0.014
			106.50	108.00	202787	1.50	0.177		0.177
			108.00	109.50	202788	1.50	0.044		0.044
108.35	129.20	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic Syenite with greenish segments. 10% subhedral et euhedral feldspars porphyries. 10% white carbonates (with sericite?) spider web veinlets all directions. 3-5% 1 to 3mm Qz-carb cross cutting 60 TCA. Not Mag. Chlorite rimmed feldspar phenocrystals. Weakly chloritized.							
108.35	129.20	Py <b>Pyrite</b> traces automorph disseminated Py	109.50	111.00	202789	1.50	0.009		0.009
110.60	112.00	Chl; Epi <b>Chloritisation; Epidotisation</b> Greenish foliated deformation zone. Massive chloritization obliterating primary porphyritic texture. Rusty lower contact. Partially epidotized. Week sericite.							
110.60	112.00	SCH <b>Schistosed</b> sickenside in schisto plans	111.00	112.50	202791	1.50	0.008		0.008
111.10	111.20	VEI;10;QzCb;;60°;; <b>Vein 10 Quartz Carbonate 60°</b> Qz-Carb-Chl veins							
112.00	129.20	Chl <b>Chloritisation</b> Week pervasive chloritization and veinlets and Qz veins borders. Chlorite rimmed feldspar phenocrystals.	112.50	114.00	202792	1.50	0.006		0.006
			114.00	115.50	202793	1.50	0.006		0.006
			115.50	117.00	202794	1.50	0.005		0.005
			117.00	118.50	202795	1.50	0.011		0.011
			118.50	120.00	202796	1.50	0.016		0.016
			120.00	121.50	202797	1.50	0.007		0.007
			121.50	123.00	202798	1.50	<0.005		0.001
			123.00	124.50	202799	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
129.20	135.80	SY; FOL <b>Syenite; Foliation</b> Grenn foliated very altered syenite. Strong chloritization and schistosity partially to totally obliterated primary porphyritic texture. When schistosity increase, lot more silica +chl+ epidote +py veins 5mm to 15mm. Chloritized and pirtized veins wall. Py traces to 1%	124.50	126.00	202800	1.50	<0.005		0.001
			126.00	127.50	202801	1.50	0.008		0.008
			127.50	129.00	202802	1.50	0.008		0.008
			129.00	130.50	202803	1.50	0.057		0.057
129.20	135.80	Chl; Epi <b>Chloritisation; Epidotisation</b> Massive chloritization giving green color to rock. Strongly epidotized segments							
129.20	135.80	FOL; FRC <b>Foliation ; Fractured</b> Strongly foliated chloritized plans (more a schistosity) 45 TCA. Rusty fractured plans 45 to 70 TCA							
129.20	135.80	Py <b>Pyrite</b> traces to 1% brassy fine Py disseminated.	130.50	132.00	202804	1.50	0.114		0.114
			132.00	133.50	202805	1.50	0.099		0.099
			133.50	135.00	202806	1.50	0.030		0.030
			135.00	136.50	202807	1.50	0.013		0.013
135.80	156.20	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic Syenite with greenish and greyish segments. 5-10% subhedral et euhedral feldspars porphyries. 10% white carbonates (with sericite?) spider web veinlets all directions. . Not Mag. Chlorite rimmed feldspar phenocrystals. Weakly chloritized. Partially silicified toward lower contact. Increasing of SF toward lower contact.	136.50	138.00	202808	1.50	0.011		0.011
			138.00	139.50	202809	1.50	<0.005		0.001
			139.50	141.00	202811	1.50	0.030		0.030
			141.00	142.50	202812	1.50	0.095		0.095
			142.50	144.00	202813	1.50	<0.005		0.001
			144.00	145.50	202814	1.50	<0.005		0.001
			145.50	147.00	202815	1.50	<0.005		0.001
			147.00	148.50	202816	1.50	<0.005		0.001
135.80	148.50	Py; Hm <b>Pyrite ; Hematite</b> Traces to 1% of very fine disseminates Py. Often more Py near Qz-Carb veins or Silica-Chl veins. Traces of hematites in veins.							
148.50	156.20	Sil; Chl <b>Silicification; Chloritisation</b> Partially silicified segments dicolorating redish syenite to grey							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
148.50	156.20	toward lower contact. Penetration of silica+Py rich fluids. 5% chlorited porphyries and veinlets Py; Hm <b>Pyrite ; Hematite</b> Fine Py disseminated 1-2%. < 1% Disseminated Hm clusters in veins	148.50	150.00	202817	1.50	0.140		0.140
			150.00	151.50	202818	1.50	0.011		0.011
			151.50	153.00	202819	1.50	0.099		0.099
			153.00	154.50	202820	1.50	0.086		0.086
			154.50	156.00	202821	1.50	0.214		0.214
			156.00	157.50	202822	1.50	1.775		1.775
156.20	177.30	SY; MNZD; POR <b>Syenite; Mineralized; Porphyric</b> Greyish with greenish redish segments mineralized porphyritic syenite. Gradual silica increasing along upper contact. Partially to strongly silicified. Silicification discoloring host rock to grey (bleaching). Very fine disseminated Py up to 5-10%. Pyrites veinlets 1%. Locally brecciated. 2-4% silica-carbonates veins. 5% white carbonates veinlets spider web texture.							
156.20	177.30	Sil <b>Silicification</b> Massive silicification to partailly silicified bleaching the host rock. Silicification overprint previous chloritization and epidotization. Argilized grennish blueish fragments in breccia (ex: 171.4m)							
156.20	177.30	Py <b>Pyrite</b> 5 to 15% fine disseminated Py. 1% Py veinlets showing flow textures. Locally disseminated or cluster of blueish very fine grain metallic minerals (could be enargite ??)	157.50	159.00	202823	1.50	2.880		2.880
			159.00	160.50	202824	1.50	1.255		1.255
			160.50	162.00	202825	1.50	1.300		1.300
			162.00	163.50	202826	1.50	0.320		0.320
			163.50	165.00	202827	1.50	0.368		0.368
			165.00	166.50	202828	1.50	0.490		0.490
			166.50	168.00	202829	1.50	0.515		0.515
			168.00	169.50	202831	1.50	1.995		1.995
			169.50	171.00	202832	1.50	2.880		2.880
			171.00	172.50	202833	1.50	1.475		1.475
			172.50	174.00	202834	1.50	1.265		1.265
			174.00	175.50	202835	1.50	0.605		0.605
			175.50	177.00	202836	1.50	0.598		0.598
			177.00	178.50	202837	1.50	1.130		1.130

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
177.30	201.00	GA; FIN <b>Gabbro; Fine grains</b> Fine grain Gabbro. Sharp upper contact at 50 TCA. Green, strongly chloritized and epidotized (Epidote out at 185.8m) well laminated in the first 5m then increasingly massive, fine grained, magnetic mafic intrusive (mag start at 185.8m). 3% of fine, smaller than 1mm yellowish leucoxene. 4-5% of millimetric white calcite veinlets and pervasive carbonatation. Partial silicification along upper contact (hydrothermal silicification out at 184.5m)  END OF HOLE AT 201m.	178.50	180.00	202838	1.50	3.150	3.13	3.130
			180.00	181.50	202839	1.50	2.540		2.540
			181.50	183.00	202841	1.50	0.728		0.728
			183.00	184.50	202842	1.50	0.104		0.104
			184.50	186.00	202843	1.50	0.015		0.015
177.30	185.80	Sil; Chl; Epi; Car <b>Silicification; Chloritisation; Epidotisation; Carbonatation</b> Partially silicified segments discolorating to grey. Strongly chloritized and epidotized. Pervasive carbonatation (very reactive to cold dilute HCL)							
177.30	185.80	Py <b>Pyrite</b> Average of 5% fine disseminated and clusters Py. % increase with silicification up to 10%.							
185.80	201.00	Chl; Car <b>Chloritisation; Carbonatation</b> Strong pervasive chloritisation and carbonatation	186.00	187.50	202844	1.50	0.019		0.019
			187.50	189.00	202845	1.50	<0.005		0.001
			189.00	190.50	202846	1.50	<0.005		0.001
			190.50	192.00	202847	1.50	<0.005		0.001
			192.00	193.50	202848	1.50	<0.005		0.001
			193.50	195.00	202849	1.50	<0.005		0.001
			195.00	196.50	202851	1.50	<0.005		0.001
			196.50	198.00	202852	1.50	<0.005		0.001
			198.00	199.50	202853	1.50	<0.005		0.001
			199.50	201.00	202854	1.50	<0.005		0.001
201.00	<b>Fin du sondage</b> Nombre d'échantillons : 127 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 190.50								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
27.00	28.50	202730	O15Pa	1.50	0.999	0.999
40.50	42.00	202740	m	1.50	<0.005	0.001
54.00	55.50	202750	O6Pc	1.50	1.630	1.630
82.50	84.00	202770	O54Pa	1.50	3.060	3.100
96.00	97.50	202780	m	1.50	0.007	0.007
109.50	111.00	202790	O61d	1.50	5.040	4.880
138.00	139.50	202810	O61d	1.50	5.030	4.840
166.50	168.00	202830	O53Pb	1.50	0.661	0.661
180.00	181.50	202840	m	1.50	0.005	0.005
193.50	195.00	202850	O15Pa	1.50	0.966	0.966



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	173.39°	-43.93°	Non	Reflex	173.00	176.90°	-44.46°	Non
Reflex	77.00	173.50°	-43.58°	Non	Reflex	176.00	176.95°	-44.39°	Non
Reflex	80.00	173.61°	-43.75°	Non	Reflex	179.00	177.10°	-44.28°	Non
Reflex	83.00	173.73°	-44.19°	Non	Reflex	182.00	177.18°	-44.36°	Non
Reflex	86.00	173.82°	-43.91°	Non	Reflex	185.00	177.32°	-44.28°	Non
Reflex	89.00	173.90°	-43.69°	Non					
Reflex	92.00	173.99°	-43.80°	Non					
Reflex	95.00	174.19°	-44.23°	Non					
Reflex	98.00	174.25°	-44.20°	Non					
Reflex	101.00	174.35°	-43.92°	Non					
Reflex	104.00	174.46°	-43.81°	Non					
Reflex	107.00	174.51°	-44.23°	Non					
Reflex	110.00	174.61°	-44.32°	Non					
Reflex	113.00	174.69°	-44.18°	Non					
Reflex	116.00	174.77°	-43.89°	Non					
Reflex	119.00	174.88°	-44.04°	Non					
Reflex	122.00	175.02°	-44.36°	Non					
Reflex	125.00	175.22°	-44.36°	Non					
Reflex	128.00	175.29°	-44.09°	Non					
Reflex	131.00	175.38°	-43.89°	Non					
Reflex	134.00	175.51°	-43.86°	Non					
Reflex	137.00	175.60°	-44.02°	Non					
Reflex	140.00	175.73°	-44.29°	Non					
Reflex	143.00	175.89°	-44.57°	Non					
Reflex	146.00	176.01°	-44.53°	Non					
Reflex	149.00	176.12°	-44.15°	Non					
Reflex	152.00	176.15°	-44.12°	Non					
Reflex	155.00	176.23°	-44.43°	Non					
Reflex	158.00	176.36°	-44.42°	Non					
Reflex	161.00	176.47°	-44.10°	Non					
Reflex	164.00	176.59°	-43.97°	Non					
Reflex	167.00	176.72°	-43.95°	Non					
Reflex	170.00	176.84°	-44.12°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	1.50	MT; MT <b>Casing; Overburden</b> Overburden 1.5m. Casing ended at 2.7m. Recuperate 1.2m of core HQ in casing from 1.5m to 2,7m. Sent all core recuperate from casing to analysis sample 202891							
0.00	16.50	FRC <b>Fractured</b> Oxydized rusty fractures 30 to 45 TCA							
1.50	2.70	MT; I2D <b>Casing; Syenite</b> Casing until 2.7m. Recuperate 1.2m of core HQ in casing from 1.5m to 2,7m. Sent all core to analysis sample 202891. Same lithology as next interval	1.50	2.70	202891	1.20	0.010		0.010
2.70	16.45	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic syenite with greenish chloritized segments. Very fractured. Oxydized rusty fractures 30 to 45 TCA. 5-10% spider web mm carbonates veinlets. 1-2% Silica-carbonates veins+Py+Hm veinsor mass. Not mag							
2.70	16.45	Oxy; Chl <b>Oxydation; Chloritisation</b> 5% rusty oxydation essentially along fractures or in veins. Chloritized to rimmed feldspars porphyries 5% and greenish foliated segments partially chloritized.							
2.70	16.50	Py; Hm0.5 <b>Pyrite ; Hematite 0.5%</b> Traces to 1% locally disseminated fine grain Py. Py boxwerk in rusty veins. Traces of Hematite in Silica-Carb veins	2.70	4.50	202855	1.80	<0.005		0.001
			4.50	6.00	202856	1.50	<0.005		0.001
			6.00	7.50	202857	1.50	<0.005		0.001
			7.50	9.00	202858	1.50	<0.005		0.001
			9.00	10.50	202859	1.50	<0.005		0.001
			10.50	12.00	202860	1.50	0.064		0.064
			12.00	13.50	202861	1.50	0.037		0.037
			13.50	15.00	202862	1.50	0.085		0.085
			15.00	16.50	202863	1.50	0.008		0.008
16.45	28.00	SY; POR; FIN <b>Syenite; Porphyric; Fine grains</b> Gradual upper contact to a greenish chloritized and epidotized medium to fine grain syenite. The primary porphyritic texture is essentially							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
16.45	28.00	<p>obliterated. 3-5% of silica + carbonates veins sometimes brecciating. Rusty oxydized cm to decimetric segments along fractures. Not mag</p> <p>Chl; Epi</p> <p><b>Chloritisation; Epidotisation</b></p> <p>Pale to medium Green pervasive chloritization and epidotisation. 5% rusty oxydation along fractures.</p>							
16.50	28.00	<p>Py</p> <p><b>Pyrite</b></p> <p>fine brassy disseminated Py 1%</p>	16.50	18.00	202864	1.50	0.058		0.058
			18.00	19.50	202865	1.50	0.005		0.005
			19.50	21.00	202866	1.50	0.005		0.005
			21.00	22.50	202867	1.50	0.007		0.007
			22.50	24.00	202868	1.50	0.017		0.017
			24.00	25.50	202869	1.50	0.012		0.012
			25.50	27.00	202871	1.50	0.009		0.009
			27.00	28.50	202872	1.50	0.008		0.008
28.00	36.10	<p>SY; POR; BR</p> <p><b>Syenite; Porphyric; Brecciated</b></p> <p>Redish partially silicified and brecciated porphyritic syenite. Network of white silica-carbonates veins brecciating locally the host rock. Not mag</p>							
28.00	36.10	<p>Sil</p> <p><b>Silicification</b></p> <p>partially silicified and brecciated</p>							
28.00	36.10	<p>Py</p> <p><b>Pyrite</b></p> <p>Traces to 1 % very fine disseminated pyrite</p>	28.50	30.00	202873	1.50	<0.005		0.001
			30.00	31.50	202874	1.50	0.034		0.034
			31.50	33.00	202875	1.50	0.032		0.032
			33.00	34.50	202876	1.50	0.036		0.036
			34.50	36.00	202877	1.50	0.090		0.090
			36.00	37.50	202878	1.50	9.290	9.22	9.220
36.10	62.20	<p>BX; MNZD; BR</p> <p><b>Breccia; Mineralized; Brecciated</b></p> <p>Medium grey to dark grey silicified mineralized hydrolic breccia. Matrix supported with minor segments clasts supported. 2mm to 4cm subangulars clasts. Clast of very altered intrusive syenite (few qz porphyries and redish syenite clasts still visibles). Matrix is essentially silica and pyrite. Clasts are often crack and/or mineralized with fine Py. 5% thin qz-carbonates spider web texture veinlets. Not mag</p>							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
36.10	62.20	Sil <b>Silicification</b> At 56.5m apparition of graphite veinlets and filling fractures 20TCA Massive silicification.3-4 Rusty oxydized fractures.							
36.10	62.20	Py <b>Pyrite</b> 5 to 15% Fine disseminated and/or smalls clusters of pyrite. Pyrite in clasts but more abundant in matrix. Fine Py veinlets 1%. Py boxwerk along rusty fractures	37.50	39.00	202879	1.50	5.850	5.56	5.560
			39.00	40.50	202881	1.50	3.260	3.17	3.170
			40.50	42.00	202882	1.50	8.250	8.14	8.140
			42.00	43.50	202883	1.50	6.070	6.00	6.000
			43.50	45.00	202884	1.50	4.590	4.19	4.190
			45.00	46.50	202885	1.50	2.560		2.560
			46.50	48.00	202886	1.50	2.710		2.710
			48.00	49.50	202887	1.50	1.130		1.130
			49.50	51.00	202888	1.50	2.460		2.460
			51.00	52.50	202889	1.50	1.540		1.540
			52.50	54.00	202892	1.50	2.160		2.160
			54.00	55.50	202893	1.50	2.150		2.150
			55.50	57.00	202894	1.50	2.760		2.760
56.40	62.00	FRC <b>Fractured</b> At 56.5m apparition of graphite veinlets and filling fractures 20TCA	57.00	58.50	202895	1.50	5.240	5.42	5.420
			58.50	60.00	202896	1.50	1.825		1.825
			60.00	61.50	202897	1.50	1.685		1.685
			61.50	63.00	202898	1.50	1.010		1.010
62.20	110.90	SY <b>Syenite</b> Greenish redish to greyish syenite. Fine grain to porphyritic texture depending on level of alteration. Upper contact 3m of greenish chloritized, epidotized foliated altered sheared transition zone. 5% thin carbonates spider web texture veinlets. 2% Grey silica-Qz-carbonates veins 2mm to cm. 1% black dark green chlorite veinlets. Brecciated segmments whre silica and qz-carb veins are more abundant. Not mag  79.8m: 10 cm silica+Py brecciated veins. 10% Py disseminated and veinlets.							
62.20	110.90	Chl; Epi; Ser; Sil <b>Chloritisation; Epidotisation; Sericitisation;</b>							

Corporation Minière Osisko Div. Exploration

Description		Analyse					
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
62.20	110.90	<b>Silicification</b>					
		Greenish segments: Chlorite-Epidote and minor sericite.					
		Pervasive, replacement and veinlets					
		Dark purple to grey : partially silicified					
		Oxydized rusty fractures					
		Py; Hm					
		<b>Pyrite ; Hematite</b>					
		1% Disseminated Py.					
		Traces of hematite in Qz-Carb veins					
		74.4-76.3m Partially silicified and brecciated segment. 10% fine Py in matrix					
74.40	76.30	63.00	64.50	202899	1.50	0.023	0.023
		64.50	66.00	202900	1.50	0.007	0.007
		66.00	67.50	202901	1.50	0.007	0.007
		67.50	69.00	202902	1.50	0.006	0.006
		69.00	70.50	202903	1.50	0.012	0.012
		70.50	72.00	202904	1.50	0.067	0.067
		72.00	73.50	202905	1.50	0.052	0.052
		73.50	75.00	202906	1.50	0.117	0.117
		75.00	76.50	202907	1.50	0.222	0.222
		76.50	78.00	202908	1.50	0.024	0.024
79.80	79.90	<b>Breccia; Brecciated</b>					
		Partially silicified breccia. 10% fine grain Py in matrix					
		78.00	79.50	202909	1.50	0.054	0.054
		79.50	81.00	202911	1.50	0.080	0.080
		81.00	82.50	202912	1.50	0.144	0.144
		82.50	84.00	202913	1.50	0.091	0.091
		84.00	85.50	202914	1.50	0.628	0.628
		85.50	87.00	202915	1.50	0.121	0.121
		87.00	88.50	202916	1.50	0.470	0.470
		88.50	90.00	202917	1.50	0.183	0.183
<b>VEI;10;::::</b>							
<b>Vein 10</b>							
10 cm silica+Py brecciated veins. 10% Py disseminated and veinlets.							
90.00	91.50	202918	1.50	0.491	0.491		
91.50	93.00	202919	1.50	0.016	0.016		
93.00	94.50	202920	1.50	0.103	0.103		
94.50	96.00	202921	1.50	0.084	0.084		
96.00	97.50	202922	1.50	0.508	0.508		
97.50	99.00	202923	1.50	0.493	0.493		
99.00	100.50	202924	1.50	0.222	0.222		
100.50	102.00	202925	1.50	0.127	0.127		
102.00	103.50	202926	1.50	0.019	0.019		
103.50	105.00	202927	1.50	0.008	0.008		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
110.90	121.50	<p>SY; MNZD; POR</p> <p><b>Syenite; Mineralized; Porphyric</b></p> <p>Sharp rusty upper contact. Dark grey purple to greenish porphyritic mineralized syenite. 5-10 % Py disseminated in matrix and veinlets. Partial to massive silicification. 10% Qz-Si-Py +- carb veins and veinlets. Small segmentsbrecciated (when Si is more intense). 5-10% Feldspars phenocrysts subhedrals sometimes partially to totally chloritized depending on the silicification level (Silicification overprinted chloritization). Not Mag. Sharp lower contact.</p>	105.00	106.50	202928	1.50	<0.005		0.001
			106.50	108.00	202929	1.50	<0.005		0.001
			108.00	109.50	202931	1.50	0.005		0.005
			109.50	111.00	202932	1.50	0.005		0.005
110.90	121.50	<p>Si; Chl</p> <p><b>Silicification; Chloritisation</b></p> <p>Partial to massive silicification overprinted preious chloritization and discoloring the rock to grey. Week chloritization still present. 5% Feldspars phenocrysts subhedrals sometimes partially to totally chloritized depending on the silicification intensity</p>							
110.90	121.50	<p>Py</p> <p><b>Pyrite</b></p> <p>5-10 % Py disseminated in matrix and veinlets. Fine grain brassy disseminated Py and very fine greyish dusty and/or brassy Py in matrix associated with silica alteration and veins</p>	111.00	112.50	202933	1.50	2.110		2.110
			112.50	114.00	202934	1.50	0.917		0.917
			114.00	115.50	202935	1.50	1.155		1.155
			115.50	117.00	P009432	1.50	0.959		0.959
			117.00	118.50	P009433	1.50	1.095		1.095
			118.50	120.00	P009434	1.50	1.110		1.110
			120.00	121.50	P009435	1.50	0.674		0.674
121.50	125.80	<p>GA; FOL</p> <p><b>Gabbro; Foliation</b></p> <p>Sharp , intrusive upper contact. Transitional zone between the mineralized syenite and the gabbro. Well foliated (at 60 TCA.) light green gabbro or a bleached syenite ? 2% of apple green chlorite shards. 3% grey silica veinsfollowing foliation</p>							
121.50	125.80	<p>Chl; Epi; Ser</p> <p><b>Chloritisation; Epidotisation; Sericitisation</b></p> <p>pervasive chlorite and epidote. Week sericite following foliation plans.</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
121.50	125.80	Py <b>Pyrite</b> 1% fine disseminated Py and veinlets in schisto plans.	121.50	123.00	P009436	1.50	0.029		0.029
			123.00	124.50	P009437	1.50	0.251		0.251
			124.50	126.00	P009438	1.50	0.074		0.074
125.80	179.50	GA <b>Gabbro</b> Gradational upper contact over 20cm. Dark green fine to medium grain gabbro, massive, not magnetic with 3% light yellow leucoxene. Strongly chloritized. Not mineralized. 2-4 % carbonates (essentially calcite) veins, disseminated in matrix and replacing feldspars. Calcites veinlets 35 TCA near bottom contact  144.5- 145.7m: Chloritized brecciated segment 148-148.7m: grey to white irregular shape Aplite veins Mag start on and off around 158m							
125.80	179.50	Chl; Car <b>Chloritisation; Carbonatisation</b> Pervasive chlorite Calcite veinlets and pervasive thru out the rock  156.4m to 158.10. 30cm to 3cm bleached grey silicified segments (4-5).							
125.80	179.50	Py <b>Pyrite</b> Not mineralized except: from:  156.4m to 158.10. 30cm to 3cm bleached grey silicified segments (4-5). 5-10% pyritized veinlets, Py disseminated and 5 to 10mm clusters	126.00	127.50	P009439	1.50	0.008		0.008
			127.50	129.00	P009440	1.50	<0.005		0.001
			129.00	130.50	P009441	1.50	<0.005		0.001
			130.50	132.00	P009442	1.50	0.009		0.009
			132.00	133.50	P009443	1.50	0.015		0.015
			133.50	135.00	P009444	1.50	<0.005		0.001
			135.00	136.50	P009446	1.50	0.023		0.023
			136.50	138.00	P009447	1.50	0.007		0.007
			138.00	139.50	P009448	1.50	0.007		0.007
			139.50	141.00	P009449	1.50	0.040		0.040
			141.00	142.50	P009450	1.50	0.029		0.029
142.50	144.00	P009451	1.50	0.060		0.060			
144.00	145.50	P009452	1.50	<0.005		0.001			
145.50	147.00	P009453	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.00	148.50	P009454	1.50	0.006		0.006
	148.50	150.00	P009455	1.50	<0.005		0.001
	150.00	151.50	P009456	1.50	<0.005		0.001
	151.50	153.00	P003937	1.50	<0.005		0.001
	153.00	154.50	P003938	1.50	0.005		0.005
	154.50	156.00	P003939	1.50	0.113		0.113
	156.00	157.50	P003940	1.50	1.990		1.990
	157.50	159.00	P003941	1.50	0.358		0.358
	159.00	160.50	P003942	1.50	0.008		0.008
	160.50	162.00	P003943	1.50	<0.005		0.001
	162.00	163.50	P003944	1.50	<0.005		0.001
	163.50	165.00	P009458	1.50	<0.005		0.001
	165.00	166.50	P009459	1.50	<0.005		0.001
	166.50	168.00	P009460	1.50	<0.005		0.001
	168.00	169.50	202974	1.50	0.007		0.007
	169.50	171.00	202975	1.50	0.006		0.006
	171.00	172.50	202976	1.50	0.006		0.006
	172.50	174.00	202977	1.50	<0.005		0.001
	174.00	175.50	202978	1.50	0.006		0.006
	175.50	177.00	202979	1.50	0.007		0.007
177.00	178.50	202981	1.50	0.006		0.006	
178.50	180.00	202982	1.50	0.007		0.007	
179.50	195.00						

SY; POR  
**Syenite; Porphyric**  
 Sharp 60 degrees TCA upper contact. Greenish redish grey porphyritic syenite. Magnetic. 5% Anhedral feldspars porphyries more or less chloritized. 2% white Qz-Carb veins and veinlet locally breccia veins  
  
 188.9m - 189.4m: Stockwerk-breccia. Chlorite veinlets and redish orange oxydized clasts.  
  
 192.8m - 195m: Dark red porphyritic rock. Red silica (jasperoide looklike) matrix. 1% fine grain disseminated sphene partially altered to leucoxene.

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
EOH : 195m									
179.50	192.80	Chl; Oxy <b>Chloritisation; Oxydation</b> Greenish to blackish chloritized segments. Chloritized veinlets and fractures (50-60 TCA)							
179.50	195.00	Mt; Py <b>Magnetite ; Pyrite</b> Magnetite veinlets and disseminated 1-2%. Traces of Py disseminated with silica veins and clusters in chlorites veins (189.3m in breccia-stockwerk segment)	180.00	181.50	202983	1.50	0.009		0.009
			181.50	183.00	202984	1.50	0.008		0.008
			183.00	184.50	202985	1.50	0.344		0.344
			184.50	186.00	202986	1.50	0.129		0.129
			186.00	187.50	202987	1.50	0.096		0.096
			187.50	189.00	202988	1.50	0.078		0.078
			189.00	190.50	202989	1.50	0.137		0.137
			190.50	192.00	202991	1.50	0.015		0.015
			192.00	193.50	202992	1.50	0.011		0.011
192.80	195.00	Sil <b>Silicification</b> Rusty oxydized sharp alteration contact. 50 TCA Red aphanitic silica (+ hematite) matrix. Jasperoide looklike	193.50	195.00	202993	1.50	0.006		0.006
195.00	Fin du sondage Nombre d'échantillons : 129 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 193.50								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
24.00	25.50	202870	O15Pa	1.50	1.020	1.020
37.50	39.00	202880	m	1.50	0.015	0.015
51.00	52.50	202890	O54Pa	1.50	2.920	2.920
78.00	79.50	202910	O15Pa	1.50	0.989	0.989
106.50	108.00	202930	O53Pb	1.50	0.624	0.624
120.00	121.50	202940	m	1.50	0.005	0.005
133.50	135.00	P009445	O52Pb	1.50	0.330	0.330
150.00	150.00	P009457	O53Pb	0.00	0.646	0.646
162.00	162.00	P003945	O54Pa	0.00	3.020	2.990
162.00	163.50	202970	O53Pb	1.50	0.554	0.554
175.50	177.00	202980	m	1.50	0.006	0.006
189.00	190.50	202990	O53Pb	1.50	0.645	0.645

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-76

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C.Corriveau, C. Gagnier

Du : 2009-11-03

Date de description : 2009-11-11

Au : 2009-11-05

Collet

Azimut : 171.80°  
 Plongée : -45.80°  
 Longueur : 156.00 m

UTM

Est	630 833.9
Nord	5 374 407.2
Élévation	314.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	170.00°	-50.65°	Non
Reflex	2.00	170.34°	-50.76°	Non
Reflex	5.00	170.86°	-50.62°	Non
Reflex	8.00	171.28°	-50.25°	Non
Reflex	11.00	171.53°	-50.44°	Non
Reflex	14.00	171.58°	-50.74°	Non
Reflex	17.00	171.74°	-50.23°	Non
Reflex	20.00	171.83°	-49.96°	Non
Reflex	23.00	171.75°	-50.09°	Non
Reflex	26.00	171.92°	-50.32°	Non
Reflex	29.00	171.97°	-50.01°	Non
Reflex	32.00	171.87°	-49.62°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	35.00	171.97°	-49.52°	Non
Reflex	38.00	172.04°	-49.85°	Non
Reflex	41.00	172.22°	-49.63°	Non
Reflex	44.00	172.25°	-49.18°	Non
Reflex	47.00	172.37°	-48.96°	Non
Reflex	50.00	172.47°	-49.18°	Non
Reflex	53.00	172.55°	-49.35°	Non
Reflex	56.00	172.66°	-49.23°	Non
Reflex	59.00	172.83°	-48.69°	Non
Reflex	62.00	172.94°	-48.53°	Non
Reflex	65.00	172.95°	-48.83°	Non
Reflex	68.00	172.86°	-48.90°	Non

Description

GPS Datum NAD83, UTM Zone 17.

A Devico multi-shot test have been used for this hole.

The single-shot Reflex tests have been corrected for magnetic declination (12.5 degrees W). Hole surveyed (Nov 2009) by Descarreaux.

A 40cm red syenite sample was recovered from the casing and sent to the lab (sample 213342).

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	71.00	172.96°	-48.31°	Non					
Reflex	74.00	173.38°	-48.26°	Non					
Reflex	77.00	173.46°	-48.64°	Non					
Reflex	80.00	173.45°	-48.09°	Non					
Reflex	83.00	173.41°	-47.92°	Non					
Reflex	86.00	173.52°	-48.27°	Non					
Reflex	89.00	173.60°	-48.00°	Non					
Reflex	92.00	173.76°	-47.87°	Non					
Reflex	95.00	173.97°	-48.06°	Non					
Reflex	98.00	174.02°	-47.40°	Non					
Reflex	101.00	174.18°	-47.82°	Non					
Reflex	104.00	174.26°	-47.59°	Non					
Reflex	107.00	174.41°	-46.99°	Non					
Reflex	110.00	174.69°	-47.23°	Non					
Reflex	113.00	174.77°	-47.34°	Non					
Reflex	116.00	174.90°	-46.78°	Non					
Reflex	119.00	175.23°	-46.61°	Non					
Reflex	122.00	175.29°	-46.70°	Non					
Reflex	125.00	175.35°	-46.97°	Non					
Reflex	128.00	175.57°	-46.60°	Non					
Reflex	131.00	175.72°	-46.30°	Non					
Reflex	134.00	175.75°	-46.50°	Non					
Reflex	137.00	175.86°	-46.67°	Non					
Reflex	140.00	176.14°	-46.36°	Non					
Reflex	143.00	176.28°	-45.91°	Non					
Reflex	146.00	176.43°	-46.12°	Non					
Reflex	149.00	176.57°	-46.20°	Non					
Reflex	152.00	176.78°	-45.66°	Non					
Reflex	155.00	176.89°	-45.38°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	4.10	MT <b>Casing</b> Casing							
4.10	4.50	SY <b>Syenite</b> 40 cm of core (HQ) recuperate while doing casing. All this core sent to lab for analysis sample 213342. Same litho as next interval	4.10	4.50	213342	0.40	0.005		0.005
4.50	20.30	SY <b>Syenite</b> Redish oxydized to greenish syenite. Medium grains Fp porphyries with fine grain matrix. Rusty fractures with Py boxwerks and Sulphides disseminated and smalls clusters (1% Py and Cp). 1-2% 2mm to 2cm Grey to white QZ + carbonates veins locally brecciated the syenite (ex: 12.1m). 4% greenish chloritized veinlets and 2% partially chloritized feldspars. Not mag.  17.3. Syenite goes to red to green. Pervasive chlorite-epidote. Partially silicified. 2% Grey fine grain silica+ Py veinlets. Lagers cm grey silica veins and pods. Transitionnal zone to the mineralized and silicified Syenite.  18- 18.5 Partially silicified, Mineralized and brecciated segments. 3% disseminated fine grain to medium grain Py. 1-2% white carbonates veinlets (all directions)  Sharp oxidized lower contact 40 degrees TCA	4.50	6.00	213343	1.50	0.006		0.006
			6.00	7.50	213344	1.50	0.022		0.022
			7.50	9.00	213345	1.50	0.011		0.011
			9.00	10.50	213346	1.50	0.039		0.039
			10.50	12.00	213347	1.50	0.006		0.006
			12.00	13.50	213348	1.50	0.008		0.008
			13.50	15.00	213349	1.50	0.005		0.005
			15.00	16.50	213351	1.50	0.006		0.006
			16.50	18.00	213352	1.50	0.099		0.099
4.50	17.30	Lim <b>Limonitisation</b>							
4.50	17.30	Py; Cp <b>Pyrite ; Chalcopyrite</b> Rusty fractures with Py boxwerks and Sulphides disseminated and smalls clusters. 1% Py and Cp							
17.30	20.30	Chl; Epi; Sil; Ser <b>Chloritisation; Epidotisation; Silicification;</b> <b>Sericitisation</b> Pervasive chlorite-epidote. Partial silicification discoloring the							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
17.30	20.30	Py <b>Pyrite</b> 3% disseminated fine grain to medium grain Py. % of sulphides increasing toward lower contact and also increasing when silicification is more important.	18.00	19.50	213353	1.50	0.053		0.053
			19.50	21.00	213354	1.50	1.025		1.025
20.30	115.40	SY; MNZ <b>Syenite; Mineralized</b> MINERALIZED ZONE. Medium grey to dark grey with greenish and dark purple segments of mineralized syenite and grey, silicified and albitized, mineralized, cherty volcanic breccia (showing shattered glass cooling fractures). More or less porphyritic depending on silicification intensity. Partially to strong silicification discoloring host rock to grey. Hydrothermal alteration Si+Py brecciating locally. 3% Late fine white carbonates veinlets spider web texture. Not mag. 1% fine black silica+Py veinlets. Gradational lower contact over 1m.  27m to 27.75: Partially silicified chlorite vein breccia parallel TCA. Traces Cp clusters.							
20.30	115.40	Sil; Chl; Ser <b>Silicification; Chloritisation; Sericitisation</b> Partial to massive silicification discoloring host rock to greyish (pervasive or veins). Greenish chloritized-sericitized. 2-4% partially chloritized porphyries.  45.1m to 47.7m 10% rusty oxydation along fractures and pervasive	21.00	22.50	213355	1.50	0.968		0.968
			22.50	24.00	213356	1.50	1.525		1.525
			24.00	25.50	213357	1.50	1.580		1.580
			25.50	27.00	213358	1.50	1.610		1.610
			27.00	28.50	213359	1.50	1.220		1.220
			28.50	30.00	213360	1.50	2.250		2.250
			30.00	31.50	213361	1.50	6.960	9.21	9.210
			31.50	33.00	213362	1.50	6.540	6.62	6.620
			33.00	34.50	213363	1.50	3.830	3.92	3.920
			34.50	36.00	213364	1.50	4.970	4.91	4.910
			36.00	37.50	213365	1.50	4.610	4.79	4.790
			37.50	39.00	213366	1.50	6.360	6.31	6.310

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
20.30	111.90	Py05 <b>Pyrite 05%</b> 3 to 8% Fine disseminated, small clusters and few stringers of Py in silicified and partially Si syenite. Traces of disseminated Cp clusters in breccia (ex:27m to 27.75m). Traces HM  Not mineralized when chlorite-epidote alteration haven't been overprinted by silica. ex: 33.05 to 33.8m  64m-64.15m Silica+Carb + Hematite+ Py veins 35 degrees TCA	39.00	40.50	213367	1.50	3.650	3.73	3.730
			40.50	42.00	213368	1.50	4.980	5.02	5.020
			42.00	43.50	213369	1.50	4.780	4.76	4.760
			43.50	45.00	213371	1.50	2.390		2.390
			45.00	46.50	213372	1.50	2.220		2.220
45.10	47.70	<b>Fractured</b> oxydized rusty fractures 20 to 45 TCA	46.50	48.00	213373	1.50	0.877		0.877
			48.00	49.50	213374	1.50	0.589		0.589
			49.50	51.00	213375	1.50	0.435		0.435
			51.00	52.50	213376	1.50	0.420		0.420
			52.50	54.00	213377	1.50	0.767		0.767
			54.00	55.50	213378	1.50	0.293		0.293
			55.50	57.00	213379	1.50	0.457		0.457
			57.00	58.50	213381	1.50	1.075		1.075
			58.50	60.00	213382	1.50	0.479		0.479
			60.00	61.50	213383	1.50	0.203		0.203
			61.50	63.00	213384	1.50	0.614		0.614
			63.00	64.50	213385	1.50	0.016		0.016
			64.50	66.00	213386	1.50	0.028		0.028
			66.00	67.50	213387	1.50	0.256		0.256
			67.50	69.00	213388	1.50	2.720		2.720
69.00	70.50	213389	1.50	3.560	3.44	3.440			
70.50	72.00	213391	1.50	5.190	5.68	5.680			
72.00	73.50	213392	1.50	2.520		2.520			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	73.50	75.00	213393	1.50	1.165		1.165
	75.00	76.50	213394	1.50	5.180	5.23	5.230
	76.50	78.00	213396	1.50	2.660		2.660
	78.00	79.90	213397	1.90	1.380		1.380
	79.90	81.00	213398	1.10	1.765		1.765
	81.00	82.50	213399	1.50	0.946		0.946
	82.50	84.00	213401	1.50	0.012		0.012
	84.00	85.50	213402	1.50	0.221		0.221
	85.50	87.00	213403	1.50	1.320		1.320
	87.00	88.50	213404	1.50	0.788		0.788
	88.50	90.00	213405	1.50	0.992		0.992
	90.00	91.50	213406	1.50	0.617		0.617
	91.50	93.00	213407	1.50	0.402		0.402
	93.00	94.50	213408	1.50	0.711		0.711
	94.50	96.00	213409	1.50	1.175		1.175
	96.00	97.50	213410	1.50	1.080		1.080
	97.50	99.00	213411	1.50	1.025		1.025
	99.00	100.50	213412	1.50	0.170		0.170
	100.50	102.00	213413	1.50	0.021		0.021
	102.00	103.50	213414	1.50	0.479		0.479
	103.50	105.00	213416	1.50	0.612		0.612
	105.00	106.50	213417	1.50	0.593		0.593
	106.50	108.00	213418	1.50	3.570	3.59	3.590
	108.00	109.50	213419	1.50	3.170	3.15	3.150
109.50	111.00	213421	1.50	1.785		1.785	
111.00	112.50	213422	1.50	7.930	7.76	7.760	
112.50	114.00	213423	1.50	4.200	4.17	4.170	
114.00	115.40	213424	1.40	2.200		2.200	
115.40	126.90	ANJ; FOL <b>Andesite; Foliation</b> Gradational upper contact over 1m. Yellow , volcanite, strongly sericitized, aphanitic, well foliated at 50 TCA. This is a transitional zone between the strongly silicified and grey mineralized volcanic above and the chloritized gabbro below. 10% of dark grey, silicified portions as in the previous unit.					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
115.40	126.90	Ser <b>Sericitisation</b> Yellowish, strongly sericitized.							
115.40	133.00	FOL <b>Foliation 70°</b>	115.40	117.00	213425	1.60	1.180		1.180
			117.00	118.50	213426	1.50	0.686		0.686
			118.50	120.00	213427	1.50	0.366		0.366
			120.00	121.50	213428	1.50	0.010		0.010
			121.50	123.00	213429	1.50	0.233		0.233
			123.00	124.50	213430	1.50	0.199		0.199
			124.50	126.90	213431	2.40	0.142		0.142
126.90	156.00	GA <b>Gabbro</b> Sharp upper contact at 60 TCA. Dark green, strongly chloritized fine to medium grain mafic intrusive (grain average: 1mm) made of 40% of light green felsic mineral (chiefly plagioclase) and 60% of mafic minerals. Not magnetic. The first 11m are foliated at 70 TCA.  EOH : 156m	126.90	129.00	213432	2.10	0.009		0.009
			129.00	130.50	213433	1.50	<0.005		0.001
			130.50	132.00	213434	1.50	0.122		0.122
			132.00	133.50	213436	1.50	0.065		0.065
			133.50	135.00	213437	1.50	<0.005		0.001
			135.00	136.50	213438	1.50	0.012		0.012
			136.50	138.00	213439	1.50	<0.005		0.001
			138.00	139.50	213441	1.50	0.006		0.006
			139.50	141.00	213442	1.50	<0.005		0.001
			141.00	142.50	213443	1.50	<0.005		0.001
			142.50	144.00	213444	1.50	<0.005		0.001
			144.00	145.50	213445	1.50	0.055		0.055
			145.50	147.00	213446	1.50	0.015		0.015
			147.00	148.50	213447	1.50	<0.005		0.001
			148.50	150.00	213448	1.50	<0.005		0.001
			150.00	151.50	213449	1.50	<0.005		0.001
			151.50	153.00	213450	1.50	<0.005		0.001
			153.00	154.50	213501	1.50	<0.005		0.001
			154.50	156.00	213502	1.50	<0.005		0.001
156.00	Fin du sondage Nombre d'échantillons : 101 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 151.90								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.00	15.00	213350	O15Pa	0.00	1.010	1.010
43.50	43.50	213370	O50Pb	0.00	0.848	0.848
57.00	57.00	213380	m	0.00	<0.005	0.001
70.50	70.50	213390	O54Pa	0.00	2.920	2.920
76.50	76.50	213395	O6Pc	0.00	1.515	1.515
82.50	82.50	213400	m	0.00	0.007	0.007
103.50	103.50	213415	O54Pa	0.00	2.930	2.930
109.50	109.50	213420	m	0.00	0.010	0.010
132.00	132.00	213435	O50Pb	0.00	0.859	0.859
138.00	138.00	213440	m	0.00	0.006	0.006

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-77	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : FORAMEX	Lot :	
Décrit par : H.Tazerout	Du : 2009-11-01	Date de description : 2009-11-18
	Au : 2009-11-03	

Collet

Azimut : 165.92°  
 Plongée : -54.70°  
 Longueur : 240.00 m

UTM

Est	630 829.8
Nord	5 374 423.7
Élévation	313.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	169.14°	-54.32°	Non
Reflex	4.00	169.23°	-53.88°	Non
Reflex	8.00	169.14°	-53.73°	Non
Reflex	12.00	169.17°	-54.12°	Non
Reflex	16.00	169.43°	-54.33°	Non
Reflex	20.00	169.61°	-54.03°	Non
Reflex	24.00	169.68°	-53.76°	Non
Reflex	28.00	169.76°	-53.76°	Non
Reflex	32.00	169.76°	-53.98°	Non
Reflex	36.00	169.77°	-53.65°	Non
Reflex	40.00	169.90°	-53.53°	Non
Reflex	44.00	169.97°	-53.45°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	48.00	170.11°	-53.92°	Non
Reflex	52.00	170.16°	-53.92°	Non
Reflex	56.00	170.29°	-52.24°	Non
Reflex	60.00	170.35°	-53.63°	Non
Reflex	64.00	170.38°	-54.01°	Non
Reflex	68.00	170.50°	-53.64°	Non
Reflex	72.00	170.54°	-53.17°	Non
Reflex	76.00	170.47°	-53.18°	Non
Reflex	80.00	170.55°	-53.35°	Non
Reflex	84.00	170.66°	-53.60°	Non
Reflex	88.00	170.79°	-53.64°	Non
Reflex	92.00	170.87°	-53.35°	Non

Description

NAD 83, UTM Zone 17

Down Hole survey were done by a Flexit shot & a multishot Devico, & they were corrected with a declination of 12.5° West (i.e. -12.5°).

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	96.00	170.99°	-53.17°	Non	Reflex	228.00	174.35°	-52.12°	Non
Reflex	100.00	170.94°	-53.10°	Non					
Reflex	104.00	170.95°	-53.53°	Non					
Reflex	108.00	171.04°	-53.60°	Non					
Reflex	112.00	171.20°	-53.17°	Non					
Reflex	116.00	171.33°	-53.02°	Non					
Reflex	120.00	171.33°	-53.04°	Non					
Reflex	124.00	171.57°	-53.45°	Non					
Reflex	128.00	171.69°	-52.89°	Non					
Reflex	132.00	171.98°	-53.32°	Non					
Reflex	136.00	172.07°	-52.79°	Non					
Reflex	140.00	172.12°	-52.76°	Non					
Reflex	144.00	172.20°	-52.96°	Non					
Reflex	148.00	172.37°	-53.20°	Non					
Reflex	152.00	172.47°	-52.98°	Non					
Reflex	156.00	172.49°	-52.62°	Non					
Reflex	160.00	172.45°	-52.72°	Non					
Reflex	164.00	172.62°	-53.08°	Non					
Reflex	168.00	172.70°	-52.79°	Non					
Reflex	172.00	172.77°	-52.70°	Non					
Reflex	176.00	172.93°	-52.86°	Non					
Reflex	180.00	172.99°	-52.50°	Non					
Reflex	184.00	173.06°	-52.52°	Non					
Reflex	188.00	173.29°	-52.79°	Non					
Reflex	192.00	173.27°	-52.48°	Non					
Reflex	196.00	173.39°	-52.15°	Non					
Reflex	200.00	173.46°	-52.62°	Non					
Reflex	204.00	173.54°	-52.48°	Non					
Reflex	208.00	173.73°	-52.12°	Non					
Reflex	212.00	173.85°	-51.84°	Non					
Reflex	216.00	173.71°	-51.85°	Non					
Reflex	220.00	173.77°	-52.11°	Non					
Reflex	224.00	173.97°	-52.26°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	4.00	MT <b>Casing</b> CASING.							
4.00	161.30	SY POR <b>Syenite Porphyry Intrusive</b> Dark red to red to dark grey to light grey to light green Chl++ & bleached+++ sections, medium grain matrix & 45-60% fids phenos<2.0cm loc. zoned & Chl++ or Alb++. Weakly to moderately foliated@40-60°TCA. Weakly fractured to loc. moderately-highly fractured and filled with a white Alb++ silica-carb fluid with local breccia cemented with a white Alb++ silica-carb fluid. Loc. broken core. 3-5% white to smokey Alb+++ VI Qtz-Carb@0-60°TCA. 7-10% light green bleached+++ & Chl++ metric sections. Loc. buff yellow Ser+ patches & specks<0.2cm. Loc. brown Oxy++/+++. Loc. Carb+ & Non Mag to loc. Mag+/+++. Tr-1% fine to coarse diss Py & Tr fine to coarse diss Cp. Lower Contact@20°TCA.	4.00	5.00	214306	1.00	0.013		0.013
			5.00	6.00	214307	1.00	0.022		0.022
			6.00	7.50	214308	1.50	0.047		0.047
			7.50	9.00	214309	1.50	<0.005		0.001
			9.00	10.50	214311	1.50	<0.005		0.001
			10.50	12.00	214312	1.50	0.016		0.016
			12.00	13.50	214313	1.50	0.013		0.013
			13.50	15.00	214314	1.50	0.237		0.237
14.50	48.10	I2D POR <b>Syenite Porphyry Intrusive</b> Same as main description, but light green bleached++ & Chl++. Foliated++@40-60°TCA. Tr-1% fine to coarse diss Py. Upper Contact@50°TCA & lower Contact@50°TCA.							
14.50	48.10	Blich80; Chl10 <b>Bleaching 80; Chloritisation 10</b> Same as main description, but light green bleached++ & Chl++. Foliated++@40-60°TCA. Upper Contact@50°TCA & lower Contact@50°TCA.	15.00	16.50	214315	1.50	0.426		0.426
			16.50	18.00	214316	1.50	0.025		0.025
			18.00	19.50	214317	1.50	0.191		0.191
			19.50	21.00	214318	1.50	0.077		0.077
			21.00	22.50	214319	1.50	0.158		0.158
			22.50	24.00	214321	1.50	0.027		0.027
			24.00	25.50	214322	1.50	0.043		0.043
			25.50	27.00	214323	1.50	0.151		0.151
			27.00	28.50	214324	1.50	0.012		0.012
			28.50	30.00	214325	1.50	<0.005		0.001
			30.00	31.50	214326	1.50	0.035		0.035
			31.50	33.00	214327	1.50	0.006		0.006
			33.00	34.50	214328	1.50	0.050		0.050
			34.50	36.00	214329	1.50	0.042		0.042
			36.00	37.50	214331	1.50	0.051		0.051
			37.50	39.00	P009461	1.50	0.147		0.147

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	39.00	40.50	P009462	1.50	0.302		0.302
	40.50	42.00	P009463	1.50	0.032		0.032
	42.00	43.50	P009464	1.50	0.108		0.108
	43.50	45.00	P009465	1.50	<0.005		0.001
	45.00	46.50	P009466	1.50	0.051		0.051
	46.50	48.00	P009467	1.50	0.055		0.055
	48.00	49.50	P009468	1.50	<0.005		0.001
	49.50	51.00	P009469	1.50	0.005		0.005
	51.00	52.50	P009470	1.50	<0.005		0.001
	52.50	54.00	P009471	1.50	0.077		0.077
	54.00	55.50	214344	1.50	<0.005		0.001
	55.50	57.00	214345	1.50	<0.005		0.001
	57.00	58.50	214346	1.50	<0.005		0.001
	58.50	60.00	214347	1.50	0.023		0.023
	60.00	61.50	214348	1.50	<0.005		0.001
	61.50	63.00	214349	1.50	<0.005		0.001
	63.00	64.50	214351	1.50	<0.005		0.001
	64.50	66.00	214352	1.50	<0.005		0.001
	66.00	67.50	214353	1.50	<0.005		0.001
	67.50	69.00	214354	1.50	0.009		0.009
	69.00	70.50	214355	1.50	<0.005		0.001
	70.50	72.00	214356	1.50	0.005		0.005
	72.00	73.50	214357	1.50	0.090		0.090
	73.50	75.00	214358	1.50	0.235		0.235
	75.00	76.50	214359	1.50	1.020		1.020
	76.50	78.00	214361	1.50	0.086		0.086
	78.00	79.50	214362	1.50	0.064		0.064
	79.50	81.00	214363	1.50	0.012		0.012
	81.00	82.50	214364	1.50	0.027		0.027
	82.50	84.00	214365	1.50	0.025		0.025
	84.00	85.50	214366	1.50	0.005		0.005
	85.50	87.00	214367	1.50	0.644		0.644
86.90 104.40 I2D POR; BR; FRA Syenite Porphyry Intrusive; Brecciated; Fractured							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
86.90	104.40	MINERALIZED ZONE: Purple-grey to dark grey to loc light buff green, fine to medium grain matrix with 25% coarse Flds phenos<2.0cm. Weakly foliated@40-60TCA. Highly fractured & highly brecciated cemented by 80% smokey silica-carb Alb+++/+++ injections. Loc. buff-light green bleached++ bands<40.0cm. 5-7% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp. Upper Contact@40TCA & Lower Contact@40-45TCA.  Py06 <b>Pyrite 06%</b> 5-7% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp.	87.00	88.50	214368	1.50	2.060	3.29	2.060
			88.50	90.00	214369	1.50	1.180		1.180
			90.00	91.50	214371	1.50	1.475		1.475
			91.50	93.00	214372	1.50	1.810		1.810
			93.00	94.50	214373	1.50	0.696		0.696
			94.50	96.00	214374	1.50	3.210		3.290
			96.00	97.50	214375	1.50	1.975		1.975
			97.50	99.00	214376	1.50	1.410		1.410
			99.00	100.50	214377	1.50	1.030		1.030
			100.50	102.00	214378	1.50	1.550		1.550
			102.00	103.50	214379	1.50	0.656		0.656
			103.50	104.40	214381	0.90	0.264		0.264
			104.40	105.00	214382	0.60	0.150		0.150
			105.00	106.50	214383	1.50	0.503		0.503
			106.50	108.00	214384	1.50	0.347		0.347
			108.00	109.50	214385	1.50	0.191		0.191
			109.50	111.00	214386	1.50	0.358		0.358
			111.00	112.50	214387	1.50	0.435		0.435
			112.50	114.00	214388	1.50	0.148		0.148
			114.00	115.50	214389	1.50	0.666		0.666
115.50	117.00	214391	1.50	0.300	0.300				
117.00	118.50	214392	1.50	0.199	0.199				
118.50	119.50	214393	1.00	0.178	0.178				
119.50	127.00	I2D LT POR; FOL <b>Syenite Lath Porphyry Intrusive 40°; Foliation</b> Grey to dark grey, fine matrix with 70% lath Flds phenos<2.0cm long & <1.0cm wide. Highly foliated @40-70TCA. Weakly							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
119.50	127.00	fractured & filled with a white-smokey Alb++/+++ silica-carb fluid. Loc. weakly brecciated cemented by a white-smokey Alb++/+++ silica-carb fluid. Loc light green alteration (?Ep/Fc?). Not MAG & not Carb. 3-5% very fine to medium diss Py & tr fine diss Cp. Upper Contact@40TCA & Lower Contact@50TCA. Py04 <b>Pyrite 04%</b> 3-5% very fine to medium diss Py & tr fine diss Cp.	119.50	120.00	214394	0.50	3.490	3.59	3.590
			120.00	121.50	214395	1.50	1.895		1.895
			121.50	123.00	214396	1.50	1.315		1.315
			123.00	124.50	214397	1.50	1.285		1.285
			124.50	126.00	214398	1.50	1.930		1.930
			126.00	127.00	214399	1.00	1.225		1.225
			127.00	139.00	Chl40; Bich30 <b>Chloritisation 40; Bleaching 30</b> Highly chloritized & highly bleached section.	127.00	127.50		214401
127.50	129.00	214402				1.50	0.977	0.977	
129.00	130.50	214403				1.50	0.930	0.930	
130.50	132.00	214404				1.50	1.395	1.395	
132.00	133.50	214405				1.50	0.665	0.665	
133.50	135.00	214406				1.50	0.053	0.053	
135.00	136.50	214407				1.50	0.216	0.216	
136.50	138.00	214408				1.50	0.032	0.032	
138.00	139.50	214409				1.50	0.025	0.025	
139.50	141.00	214411				1.50	0.011	0.011	
141.00	142.50	214412				1.50	0.007	0.007	
142.50	144.00	214413				1.50	1.105	1.105	
144.00	145.50	214414				1.50	0.660	0.660	
145.50	147.00	214415				1.50	0.432	0.432	
147.00	148.50	214416				1.50	0.205	0.205	
148.50	150.00	214417				1.50	0.180	0.180	
150.00	151.50	214418				1.50	0.503	0.503	
151.50	153.00	214419	1.50	0.378	0.378				
153.00	154.50	214421	1.50	0.694	0.694				
154.50	156.00	214422	1.50	0.440	0.440				
156.00	157.50	214423	1.50	0.563	0.563				
157.50	159.00	214424	1.50	1.250	1.250				

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			159.00	160.50	214425	1.50		0.224		0.224
			160.50	161.30	214426	0.80		0.295		0.295
127.00	136.50	BRK <b>Broken</b> 40% broken core.								
161.30	240.00	GA <b>Gabbro</b> Green to dark green, fine to medium grain at the upper contact & coarse grain overall, weakly to moderately foliated@30-70TCA. Highly Chloritized. Tr fine diss Py. Upper Contact@20TCA.  E.O.H.: 240.00m.	161.30	162.00	214427	0.70		1.690		1.690
			162.00	163.50	214428	1.50		1.890		1.890
			163.50	165.00	214429	1.50		0.345		0.345
			165.00	166.50	214431	1.50		0.109		0.109
			166.50	168.00	D519282	1.50		0.076		0.076
			168.00	169.50	D519283	1.50		0.080		0.080
			169.50	171.00	D519284	1.50		0.007		0.007
			171.00	172.50	D519285	1.50		0.006		0.006
			172.50	174.00	D519286	1.50		0.013		0.013
			174.00	175.50	D519287	1.50		0.005		0.005
			175.50	177.00	D519288	1.50		0.005		0.005
			177.00	178.50	D519289	1.50		0.005		0.005
			178.50	180.00	D519291	1.50		<0.005		0.001
			180.00	181.50	D519292	1.50		<0.005		0.001
			181.50	183.00	D519294	1.50		<0.005		0.001
			183.00	184.50	D519295	1.50		<0.005		0.001
			184.50	186.00	D519296	1.50		<0.005		0.001
			186.00	187.50	D519297	1.50		0.005		0.005
			187.50	189.00	D519298	1.50		<0.005		0.001
			189.00	190.50	D519299	1.50		<0.005		0.001
			190.50	192.00	D519300	1.50		<0.005		0.001
			192.00	193.50	D519301	1.50		<0.005		0.001
			193.50	195.00	D519302	1.50		<0.005		0.001
			195.00	196.50	D519303	1.50		<0.005		0.001
			196.50	198.00	D519304	1.50		<0.005		0.001
			198.00	199.50	D519305	1.50		<0.005		0.001
			199.50	201.00	D519306	1.50		0.005		0.005
			201.00	202.50	D519307	1.50		0.016		0.016
			202.50	204.00	D519308	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			204.00	205.50	D519309	1.50		0.005		0.005
			205.50	207.00	D519311	1.50		<0.005		0.001
			207.00	208.50	D519312	1.50		<0.005		0.001
			208.50	210.00	D519314	1.50		0.005		0.005
			210.00	211.50	D519315	1.50		<0.005		0.001
			211.50	213.00	D519316	1.50		<0.005		0.001
			213.00	214.50	D519317	1.50		<0.005		0.001
			214.50	216.00	D519318	1.50		<0.005		0.001
			216.00	217.50	D519319	1.50		<0.005		0.001
			217.50	219.00	D519321	1.50		<0.005		0.001
			219.00	220.50	D519322	1.50		<0.005		0.001
			220.50	222.00	D519323	1.50		<0.005		0.001
			222.00	223.50	D519324	1.50		<0.005		0.001
			223.50	225.00	D519325	1.50		<0.005		0.001
			225.00	226.50	D519326	1.50		0.094		0.094
			226.50	228.00	D519327	1.50		<0.005		0.001
			228.00	229.50	D519328	1.50		<0.005		0.001
			229.50	231.00	D519329	1.50		<0.005		0.001
			231.00	232.50	D519331	1.50		<0.005		0.001
			232.50	234.00	D519332	1.50		<0.005		0.001
			234.00	235.50	D519334	1.50		<0.005		0.001
			235.50	237.00	D519335	1.50		<0.005		0.001
			237.00	238.50	214432	1.50		0.252		0.252
			238.50	240.00	214433	1.50		0.212		0.212
238.80	240.00	I2D POR <b>Syenite Porphyry Intrusive 20°</b> Dark grey, medium to coarse grain matrix, 10% barely visible Flds phenos<1.0cm. Tr-1% very fine to medium diss Py.  Upper contact@20TCA.								
240.00		Fin du sondage Nombre d'échantillons : 162 Nombre d'échantillons QAQC : 19 Longueur totale échantillonnée : 236.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.50	9.00	214310	m	1.50	<0.005	0.001
21.00	22.50	214320	O53Pb	1.50	0.604	0.604
34.50	36.00	214330	m	1.50	<0.005	0.001
61.50	63.00	214350	m	1.50	<0.005	0.001
75.00	76.50	214360	O6Pc	1.50	1.515	1.515
88.50	90.00	214370	m	1.50	<0.005	0.001
102.00	103.50	214380	O6Pc	1.50	1.530	1.530
114.00	115.50	214390	m	1.50	0.009	0.009
126.00	127.00	214400	O6Pc	1.00	1.590	1.590
138.00	139.50	214410	m	1.50	0.005	0.005
151.50	153.00	214420	O53Pb	1.50	0.673	0.673
163.50	165.00	214430	m	1.50	0.005	0.005
178.50	180.00	D519290	O54Pa	1.50	3.030	3.030
180.00	181.50	D519293	D519292	1.50	<0.005	0.001
205.50	207.00	D519310	O61d	1.50	4.860	4.860
207.00	208.50	D519313	D519312	1.50	<0.005	0.001
217.50	219.00	D519320	m	1.50	<0.005	0.001
231.00	232.50	D519330	O50Pb	1.50	0.844	0.844
232.50	234.00	D519333	D519332	1.50	<0.005	0.001





Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	106.00	172.62°	-45.12°	Non					
Reflex	110.00	172.75°	-44.82°	Non					
Reflex	114.00	173.04°	-44.76°	Non					
Reflex	118.00	173.31°	-44.61°	Non					
Reflex	122.00	173.26°	-44.98°	Non					
Reflex	126.00	173.40°	-44.40°	Non					
Reflex	130.00	173.44°	-44.86°	Non					
Reflex	134.00	173.55°	-45.02°	Non					
Reflex	138.00	173.78°	-44.66°	Non					
Reflex	142.00	173.96°	-44.65°	Non					
Reflex	146.00	174.01°	-44.24°	Non					
Reflex	150.00	174.14°	-44.49°	Non					
Reflex	154.00	174.16°	-45.90°	Non					
Reflex	158.00	174.28°	-44.60°	Non					
Reflex	162.00	174.32°	-44.42°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.60	MT <b>Overburden</b>							
2.60	138.30	SY POR; FRA <b>Syenite Porphyry Intrusive; Fractured</b> Casing to 4m. Red to reddish-green to light green, fine grained matrix, 20-30% Flds phenos< 2.0cm loc chl+ /+++ . Weak to moderately fractured to loc. highly fractured with multiple generation injection of a white-smokey Alb++ Qtz-Carb fluid. Loc. hydro-brecciated cemented by a white-smokey Alb++ Qtz-Carb fluid. 7-10% white-smokey injected & VI Qtz-Carb@10-80TCA<5.0cm. Loc. fractures filled with a dark-grey graphite<0.2cm. Loc broken core. 3-5% light green-buff-yellowish Ser+ /++ in bands<~50.0cm and in patches<~10.0cm. Loc. brown Oxy+ /+++ . Mineralized & highly silicified injected zone start at 15.00-###.###m. 1% very fine to coarse diss Py overall with loc. 12-15% very fine to medium diss Py. Non carb. Non Mag. Inf. Contact@##TCA.	4.00	5.00	214204	1.00	0.092		0.092
			5.00	6.00	214205	1.00	0.317		0.317
			6.00	7.50	214206	1.50	0.214		0.214
			7.50	9.00	214207	1.50	0.006		0.006
			9.00	10.50	214208	1.50	0.101		0.101
			10.50	12.00	214209	1.50	0.178		0.178
			12.00	13.50	214210	1.50	0.014		0.014
			13.50	15.00	214211	1.50	0.005		0.005
15.00	39.00	I2D POR; BR; FRA <b>Syenite Porphyry Intrusive; Brecciated; Fractured</b> MINERALIZED ZONE: Purple-grey to dark grey to loc light buff green, fine to medium grain matrix with 25% coarse Flds phenos<2.0cm. Moderatly foliated@40-60TCA. Highly fractured & highly brecciated cemented by 80% smokey silica-carb Alb+ /+++ injections. Loc. buff-light green bleached++ bands<40.0cm. 10-12% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp. Upper Contact@45TCA & Lower Contact@40TCA.							
15.00	39.00	FRC; BRE <b>Fractured ; Breccia</b> Moderatly foliated@40-60TCA. Highly fractured & highly brecciated cemented by 80% smokey silica-carb Alb+ /+++ injections.							
15.00	39.00	Py12 <b>Pyrite 12%</b> 10-12% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp.	15.00	16.50	214212	1.50	0.552		0.552
			16.50	18.00	214213	1.50	1.685		1.685
			18.00	19.50	214214	1.50	2.730		2.730
			19.50	21.00	214215	1.50	2.290		2.290
			21.00	22.50	214216	1.50	0.759		0.759

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	22.50	24.00	214217	1.50	0.952		0.952
	24.00	25.50	214218	1.50	1.780		1.780
	25.50	27.00	214219	1.50	0.890		0.890
	27.00	28.50	214220	1.50	1.165		1.165
	28.50	30.00	214221	1.50	0.382		0.382
	30.00	31.50	214222	1.50	0.403		0.403
	31.50	33.00	214223	1.50	0.528		0.528
	33.00	34.50	214224	1.50	2.480		2.480
	34.50	36.00	214225	1.50	2.250		2.250
	36.00	37.50	214226	1.50	1.210		1.210
	37.50	39.00	214227	1.50	0.779		0.779
	39.00	40.50	214228	1.50	0.573		0.573
	40.50	42.00	214229	1.50	0.472		0.472
	42.00	43.50	214231	1.50	0.193		0.193
	43.50	45.00	214232	1.50	0.852		0.852
	45.00	46.50	214233	1.50	0.372		0.372
	46.50	48.00	214234	1.50	0.236		0.236
	48.00	49.50	214235	1.50	0.236		0.236
	49.50	51.00	214236	1.50	0.019		0.019
	51.00	52.50	214237	1.50	0.021		0.021
	52.50	54.00	214238	1.50	0.172		0.172
	54.00	55.50	214239	1.50	0.160		0.160
	55.50	57.00	214241	1.50	0.542		0.542
	57.00	58.50	214242	1.50	1.220		1.220
	58.50	60.00	214243	1.50	0.200		0.200
	60.00	61.50	214244	1.50	0.684		0.684
	61.50	63.00	214245	1.50	0.187		0.187
	63.00	64.50	214246	1.50	0.193		0.193
	64.50	66.00	214247	1.50	0.186		0.186
	66.00	67.50	214248	1.50	0.041		0.041
	67.50	69.00	214249	1.50	0.128		0.128
	69.00	70.50	214251	1.50	0.217		0.217
	70.50	72.00	214252	1.50	0.313		0.313

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
72.00	99.15	I2D POR; FRA; BR <b>Syenite Porphyry Intrusive; Fractured; Brecciated</b> MINERALIZED ZONE: Purple-grey to dark grey to loc light buff green, fine to medium grain matrix with 25% coarse Flds phenos<2.0cm. Weakly foliated@40-60TCA. Moderatly fractured & weakly to moderatly brecciated cemented by 40% smokey silica-carb Alb++/+++ injections. Loc. buff-light green bleached++ bands<40.0cm. 2-3% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp.							
72.00	99.15	Py2.5 <b>Pyrite 2.5%</b> 2-3% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm. Tr fine diss Cp.	72.00	73.50	214253	1.50	0.348		0.348
			73.50	75.00	214254	1.50	1.315		1.315
			75.00	76.50	214255	1.50	0.604		0.604
			76.50	78.00	214256	1.50	0.498		0.498
			78.00	79.50	214257	1.50	0.401		0.401
			79.50	81.00	214258	1.50	0.201		0.201
			81.00	82.50	214259	1.50	2.970		2.970
			82.50	84.00	214261	1.50	1.370		1.370
			84.00	85.50	214262	1.50	2.180		2.180
			85.50	87.00	214263	1.50	4.600	4.77	4.770
			87.00	88.50	214264	1.50	0.441		0.441
			88.50	90.00	214265	1.50	1.355		1.355
			90.00	91.50	214266	1.50	0.285		0.285
			91.50	93.00	214267	1.50	1.125		1.125
			93.00	94.50	214268	1.50	0.010		0.010
			94.50	96.00	214269	1.50	0.468		0.468
			96.00	97.50	214271	1.50	0.009		0.009
			97.50	99.00	214272	1.50	0.019		0.019
			99.00	100.50	214273	1.50	0.124		0.124
99.15	104.20	I2D LT POR; FOL <b>Syenite Lath Porphyry Intrusive; Foliation</b> Dark purple-grey to dark grey, fine matrix with 70% lath Flds phenos<2.0cm long & <1.0cm wide. Highly foliated @40-70TCA. Moderatly to highly fractured & filled with a white-smokey Alb++/+++ silica-carb fluid. Loc. moderatly brecciated cemented	100.50	102.00	214274	1.50	0.249		0.249
			102.00	103.50	214275	1.50	0.452		0.452
			103.50	104.20	214276	0.70	0.780		0.780

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
104.20	110.50	by a white-smokey Alb+/+++ silica-carb fluid. Loc light green alteration (?Ep/Fc?). Not MAG & not Carb. 3-5% very fine to medium diss Py & tr fine diss Cp. Upper Contact@35-40TCA & Lower Contact@60TCA. I2D POR; BR; FRA <b>Syenite Porphyry Intrusive; Brecciated; Fractured</b> MINERALIZED ZONE: Purple-grey to dark grey to loc light buff green, fine to medium grain matrix with 10% coarse Flds phenos<2.0cm. Weakly to moderately foliated@40-60TCA. Moderately fractured & Weakly to moderately brecciated cemented by 80% smokey silica-carb Alb+/+++ injections. Loc. buff-light green bleached++ bands<40.0cm. 2-3% very fine to medium diss Py, Py seamlets<0.5cm along fractures & along foliation, & coarse Py clusters<2.0cm & Tr-1% fine silver sulphides (AsPy?) & Tr fine diss Cp. Upper Contact@60TCA & Lower Contact@40TCA.						
		104.20	105.00	214277	0.80	0.291		0.291
		105.00	106.50	214278	1.50	0.875		0.875
		106.50	108.00	214279	1.50	0.725		0.725
		108.00	109.50	214281	1.50	0.207		0.207
		109.50	110.50	214282	1.00	1.120		1.120
110.50	138.30	I2D POR <b>Syenite Porphyry Intrusive</b> Same as main lithology but 80% light green highly bleached core & mediumly to loc. coarse grain matrix. Phenos are difficult to see. Tr fine to coarse diss Py. Lower Contact@60TCA.						
		110.50	111.00	214283	0.50	0.093		0.093
		111.00	112.50	214284	1.50	0.129		0.129
		112.50	114.00	214285	1.50	<0.005		0.001
		114.00	115.50	214286	1.50	0.005		0.005
		115.50	117.00	214287	1.50	<0.005		0.001
		117.00	118.50	214288	1.50	<0.005		0.001
		118.50	120.00	214289	1.50	<0.005		0.001
		120.00	121.50	214291	1.50	0.059		0.059
		121.50	123.00	214292	1.50	<0.005		0.001
		123.00	124.50	214293	1.50	<0.005		0.001
		124.50	126.00	214294	1.50	<0.005		0.001
		126.00	127.50	214295	1.50	0.026		0.026
		127.50	129.00	214296	1.50	0.564		0.564
		129.00	130.50	214297	1.50	0.062		0.062
		130.50	132.00	214298	1.50	0.167		0.167
		132.00	133.50	214299	1.50	0.219		0.219
		133.50	135.00	214301	1.50	0.015		0.015
		135.00	136.50	214302	1.50	0.648		0.648
		136.50	138.00	214303	1.50	0.112		0.112
		138.00	139.50	214304	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
138.30	168.00	GA	139.50	141.00	214305	1.50	0.005		0.005
		<b>Gabbro</b>	141.00	142.50	223329	1.50	0.008		0.008
		Green to dark green, fine to medium grain at the upper contact & coarse grain overall,	142.50	144.00	223330	1.50	0.365		0.365
		weakly to moderately foliated@60-80TCA. Highly Chloritized. Tr fine diss Py.	144.00	145.50	223331	1.50	0.006		0.006
		Upper Contact@60TCA.	145.50	147.00	223332	1.50	0.008		0.008
			147.00	148.50	223333	1.50	<0.005		0.001
			148.50	150.00	223334	1.50	<0.005		0.001
		E.O.H.: 168.00m.	150.00	151.50	223335	1.50	<0.005		0.001
			151.50	153.00	223336	1.50	<0.005		0.001
			153.00	154.50	223337	1.50	<0.005		0.001
			154.50	156.00	223338	1.50	<0.005		0.001
			156.00	157.50	223339	1.50	<0.005		0.001
			157.50	159.00	223340	1.50	<0.005		0.001
			159.00	160.50	223342	1.50	<0.005		0.001
			160.50	162.00	223343	1.50	<0.005		0.001
			162.00	163.50	223345	1.50	<0.005		0.001
			163.50	165.00	223346	1.50	<0.005		0.001
			165.00	166.50	223347	1.50	0.330		0.330
			166.50	168.00	223349	1.50	0.304		0.304
168.00		Fin du sondage Nombre d'échantillons : 112 Nombre d'échantillons QAQC : 11 Longueur totale échantillonnée : 164.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
40.50	42.00	214230	m	1.50	<0.005	0.001
54.00	55.50	214240	O53Pb	1.50	0.651	0.651
67.50	69.00	214250	m	1.50	<0.005	0.001
81.00	82.50	214260	O6Pc	1.50	1.530	1.530
94.50	96.00	214270	m	1.50	<0.005	0.001
106.50	108.00	214280	O6Pc	1.50	1.500	1.500
118.50	120.00	214290	m	1.50	<0.005	0.001
132.00	133.50	214300	O53Pb	1.50	0.625	0.625
157.50	157.50	223341	O52Pb	0.00	0.332	0.332
160.50	162.00	223344	223343	1.50	<0.005	0.001
165.00	165.00	223348	m	0.00	<0.005	0.001



## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-79

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie Mine Site

Foré par : Foramex

Lot :

Décrit par : C. Gagnier and F. Archibald

Du : 2009-11-07

Date de description : 2009-11-20

Au : 2009-11-10

Collet

UTM

Azimut : 170.33°

Plongée : -55.70°

Longueur : 297.00 m

Est 630 852.1

Nord 5 374 435.6

Élévation 312.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	15.00	170.00°	-55.00°	Non
Reflex	18.00	174.00°	-56.30°	Non
Reflex	21.00	174.60°	-56.60°	Non
Reflex	24.00	174.10°	-56.50°	Non
Reflex	27.00	175.20°	-56.50°	Non
Reflex	30.00	175.60°	-56.40°	Non
Reflex	33.00	175.10°	-56.40°	Non
Reflex	36.00	174.10°	-56.30°	Non
Reflex	39.00	174.10°	-56.30°	Non
Reflex	42.00	175.30°	-56.30°	Non
Reflex	45.00	175.30°	-56.40°	Non
Reflex	48.00	175.80°	-56.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	51.00	176.20°	-56.60°	Non
Reflex	54.00	176.20°	-56.50°	Non
Reflex	57.00	175.30°	-56.40°	Non
Reflex	60.00	175.50°	-56.50°	Non
Reflex	63.00	176.00°	-56.50°	Non
Reflex	66.00	175.80°	-56.50°	Non
Reflex	69.00	174.90°	-56.50°	Non
Reflex	72.00	174.70°	-56.60°	Non
Reflex	75.00	174.90°	-56.50°	Non
Reflex	78.00	175.40°	-56.60°	Non
Reflex	81.00	176.20°	-56.70°	Non
Reflex	84.00	176.70°	-56.60°	Non

Description

GPS Datum NAD83, UTM Zone 17.

The Flexit single-shot tests were corrected for magnetic declination (12.5 degrees to the west). A Reflex multi-shot was used and also corrected for mag declination. Surveyed (Nov 2009) by Descarreaux.

60cm of core was recovered from the casing section and sent to the lab (sample 213503).

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	87.00	177.20°	-56.60°	Non
Reflex	90.00	177.90°	-56.70°	Non
Reflex	93.00	176.70°	-56.50°	Non
Reflex	96.00	177.30°	-56.90°	Non
Reflex	99.00	178.40°	-56.70°	Non
Reflex	102.00	177.80°	-56.80°	Non
Reflex	105.00	178.00°	-56.90°	Non
Reflex	108.00	178.40°	-56.80°	Non
Reflex	111.00	177.50°	-56.80°	Non
Reflex	114.00	177.00°	-56.90°	Non
Reflex	117.00	177.10°	-56.90°	Non
Reflex	120.00	178.60°	-56.90°	Non
Reflex	123.00	178.30°	-57.00°	Non
Reflex	126.00	178.30°	-57.00°	Non
Reflex	129.00	178.40°	-57.00°	Non
Reflex	132.00	178.70°	-56.90°	Non
Reflex	135.00	178.80°	-56.90°	Non
Reflex	138.00	178.20°	-57.10°	Non
Reflex	141.00	178.10°	-57.00°	Non
Reflex	144.00	179.00°	-57.00°	Non
Reflex	147.00	178.70°	-57.00°	Non
Reflex	150.00	179.30°	-56.80°	Non
Reflex	153.00	179.30°	-56.90°	Non
Reflex	156.00	179.50°	-56.80°	Non
Reflex	159.00	178.90°	-56.80°	Non
Reflex	162.00	179.50°	-56.90°	Non
Reflex	165.00	180.10°	-56.90°	Non
Reflex	168.00	180.00°	-56.90°	Non
Reflex	171.00	179.40°	-56.80°	Non
Reflex	174.00	179.90°	-56.80°	Non
Reflex	177.00	180.20°	-56.80°	Non
Reflex	180.00	180.70°	-56.70°	Non
Reflex	183.00	179.40°	-56.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	186.00	181.10°	-56.90°	Non
Reflex	189.00	181.10°	-57.00°	Non
Reflex	192.00	180.70°	-57.00°	Non
Reflex	195.00	180.40°	-56.90°	Non
Reflex	198.00	180.70°	-56.90°	Non
Reflex	201.00	180.50°	-56.90°	Non
Reflex	204.00	180.70°	-57.00°	Non
Reflex	207.00	180.40°	-56.90°	Non
Reflex	210.00	180.50°	-56.80°	Non
Reflex	213.00	180.90°	-56.90°	Non
Reflex	216.00	181.00°	-56.80°	Non
Reflex	219.00	181.10°	-56.80°	Non
Reflex	222.00	181.70°	-57.00°	Non
Reflex	225.00	179.90°	-56.90°	Non
Reflex	228.00	180.20°	-56.80°	Non
Reflex	231.00	180.50°	-56.80°	Non
Reflex	234.00	180.20°	-56.70°	Non
Reflex	237.00	182.30°	-56.80°	Non
Reflex	240.00	180.70°	-56.70°	Non
Reflex	243.00	181.00°	-56.90°	Non
Reflex	246.00	182.30°	-56.80°	Non
Reflex	249.00	181.20°	-56.80°	Non
Reflex	252.00	181.70°	-56.80°	Non
Reflex	255.00	180.90°	-56.90°	Non
Reflex	258.00	181.70°	-56.80°	Non
Reflex	261.00	182.00°	-56.80°	Non
Reflex	264.00	183.00°	-56.60°	Non
Reflex	267.00	184.70°	-56.60°	Non
Reflex	270.00	184.00°	-56.40°	Non
Reflex	273.00	188.00°	-56.40°	Non
Reflex	276.00	185.60°	-56.30°	Non
Reflex	279.00	189.40°	-56.10°	Non
Reflex	282.00	185.20°	-56.10°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	285.00	185.10°	-56.00°	Non					
Reflex	288.00	186.00°	-56.10°	Non					
Reflex	291.00	184.20°	-56.20°	Non					
Reflex	294.00	185.80°	-56.00°	Non					
Reflex	297.00	185.10°	-56.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.40	MT <b>overburden</b> Casing up to 3m.							
2.40	83.40	SY; POR <b>Syenite; Porphyric</b> Casing at 3m. A 60cm of HQ size core of red syenite was recovered from the casing portion (core from 2.4 to 3m): well foliated at 70 TCA, weakly chloritized with 5% of 1cm white quartz-carbonate veins at 85 TCA. Not mineralized.  Onward from 3m: red brick, massive porphyry syenite with less than 15% of anhedral, chloritized feldspar phenocrystals smaller than 1cm (average size: 5mm). Not magnetic. The first meters (from 3m to 6m) is well foliated at 70 TCA. The unit becomes locally greenish when chloritized. Locally cross-cut by thin, millimetric white carbonate veinlets generally at 60 TCA. Locally brecciated.	2.40	3.00	213503	0.60	0.045		0.045
3.00	15.00	Wea <b>Weathering (incl. Saprolitic alter.)</b> Intensely hematized broken core.							
3.00	15.00	FRC <b>Fractured</b>	3.00	4.50	213504	1.50	0.016		0.016
			4.50	6.00	213505	1.50	0.338		0.338
			6.00	7.50	213506	1.50	0.050		0.050
			7.50	9.00	213507	1.50	0.033		0.033
			9.00	10.50	213508	1.50	0.438		0.438
10.40	10.80	VEI;40;QzCbLm;;00; <b>Vein 40 Quartz Carbonate Limonite 00%</b> A 40cm white chiefly quartz with minor carbonate and iron oxydes filling a weak porosity. No sulfides.	10.50	12.00	213509	1.50	0.188		0.188
			12.00	13.50	213510	1.50	0.005		0.005
			13.50	15.00	213511	1.50	0.371		0.371
			15.00	16.50	213512	1.50	0.150		0.150
			16.50	18.00	213513	1.50	0.017		0.017
			18.00	19.50	213514	1.50	0.018		0.018
			19.50	21.00	213516	1.50	0.007		0.007
			21.00	22.50	213517	1.50	0.017		0.017
21.50	28.00	Chl <b>Chloritisation</b> Weak pervasive chloritization.	22.50	24.00	213518	1.50	<0.005		0.001
			24.00	25.50	213519	1.50	0.017		0.017
			25.50	27.00	213521	1.50	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
26.90	27.20	VEI;30;QzCb;;85°;00; <b>Vein 30 Quartz Carbonate 85° 00%</b> 30 cm of a white quartz and carbonate barren vein at 85 TCA.	27.00	28.50	213522	1.50	0.012		0.012
			28.50	30.00	213523	1.50	<0.005		0.001
			30.00	31.50	213524	1.50	<0.005		0.001
			31.50	33.00	213525	1.50	0.031		0.031
			33.00	34.50	213526	1.50	0.020		0.020
			34.50	36.00	213527	1.50	0.010		0.010
			36.00	37.50	213528	1.50	<0.005		0.001
			37.50	39.00	213529	1.50	<0.005		0.001
			39.00	40.50	213530	1.50	<0.005		0.001
			40.50	42.00	213531	1.50	<0.005		0.001
			42.00	43.50	213532	1.50	<0.005		0.001
			43.50	45.00	213533	1.50	<0.005		0.001
			45.00	46.50	213534	1.50	0.135		0.135
45.40	47.10	Ser <b>Sericitisation</b> Light greenish sericite ?							
45.40	47.10	Py0.5 <b>Pyrite 0.5%</b> Light greenish portion (sericitized ?) with 0.5% pyrite.	46.50	48.00	213536	1.50	0.013		0.013
			48.00	49.50	213537	1.50	<0.005		0.001
			49.50	51.00	213538	1.50	0.006		0.006
			51.00	52.50	213539	1.50	0.066		0.066
51.10	52.60	Ser <b>Sericitisation</b> Light greenish sericite ?							
51.10	52.60	Py0.5 <b>Pyrite 0.5%</b> Light greenish portion (sericitized ?) with 0.5% pyrite.	52.50	54.00	213541	1.50	<0.005		0.001
			54.00	55.50	213542	1.50	<0.005		0.001
			55.50	57.00	213543	1.50	<0.005		0.001
			57.00	58.50	213544	1.50	<0.005		0.001
			58.50	60.00	213545	1.50	<0.005		0.001
			60.00	61.50	213546	1.50	<0.005		0.001
			61.50	63.00	213547	1.50	<0.005		0.001
			63.00	64.50	213548	1.50	<0.005		0.001
			64.50	66.00	213549	1.50	<0.005		0.001
			66.00	67.50	213550	1.50	<0.005		0.001
67.50	69.00	212596	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
68.50	68.90	FRC <b>Fractured</b>	69.00	70.50	212597	1.50	<0.005		0.001
			70.50	72.00	212598	1.50	<0.005		0.001
			72.00	73.50	212599	1.50	0.030		0.030
			73.50	75.00	212601	1.50	0.646		0.646
			75.00	76.50	212602	1.50	0.096		0.096
			76.50	78.00	212603	1.50	<0.005		0.001
			78.00	79.50	212604	1.50	<0.005		0.001
			79.50	81.00	212605	1.50	0.015		0.015
			81.00	82.20	212606	1.20	<0.005		0.001
	82.20	83.40	212607	1.20	<0.005		0.001		
83.40	108.50	SY; MNZ <b>Syenite; Mineralized</b> RW ZONE. Gradational upper contact over 10cm. Strongly altered and locally mineralized syenite. The first 7m are apple-green, sericitized; onward, the unit is silicified and greyish. Locally mineralized.	83.40	85.50	212608	2.10	0.145		0.145
			85.50	87.00	212609	1.50	0.076		0.076
			87.00	88.50	212610	1.50	0.672		0.672
			88.50	90.00	212611	1.50	0.484		0.484
83.40	87.30	Ser <b>Sericitisation</b> Apple-green sericite.							
83.40	87.30	Py0.5 <b>Pyrite 0.5%</b> RW ZONE.							
90.00	98.60	I2D; MAS <b>Syenite; Massive rock</b> pink color, coarse grained, becoming slightly altered and silicious after 97.2m with brecciated feldspathic seams, becoming mineralized after 98.2m with localized seams and disseminated pyrite (-0.5%).	90.00	91.50	212612	1.50	0.423		0.423
			91.50	93.00	212613	1.50	0.582		0.582
			93.00	94.50	212614	1.50	0.300		0.300
			94.50	96.00	212615	1.50	0.011		0.011
			96.00	97.50	212616	1.50	0.043		0.043
			97.50	99.00	212617	1.50	0.741		0.741
98.60	108.50	I2D <b>Syenite</b> Mineralized syenite porphyry intrusive zone. Dark grey cherty textured-brecciated with albitized seams starting at 107m, up to 1.5% disseminated and seam pyrite in localized sections, becoming more siliceous after 102.2m depth with increase to 1.5% to 2% pyrite in localized sections (seams and disseminated). At 107.75m: black chlorite-specular hematite-graphite rich seams (very fine grained) with bleached pyrite due to	99.00	100.50	212618	1.50	1.135		1.135
			100.50	102.00	212619	1.50	3.330	3.35	3.350
			102.00	103.50	212620	1.50	1.915		1.915
			103.50	105.00	212621	1.50	2.040		2.040
			105.00	106.50	212622	1.50	1.895	1.91	1.905
			106.50	108.00	212623	1.50	2.340		2.340
			108.00	108.50	212624	0.50	0.796		0.796

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
108.50	138.30	SY <b>Syenite</b> Pink-green color, slight feldspathic fracturing, some grey-siliceous seams (brecciated) increasing from 115.0 to 121.0m depth but generally low localized seams pyrite with chert/fuchite/albite/chlorite rich seams (hydrothermally altered).	108.50	110.00	212625	1.50	0.225	0.225
			110.00	110.60	212626	0.60	0.974	0.974
			110.60	111.10	212627	0.50	0.222	0.222
			111.10	112.50	D519336	1.40	0.090	0.090
			112.50	114.00	D519337	1.50	0.015	0.015
			114.00	115.40	D519338	1.40	0.135	0.135
			115.40	116.15	D519339	0.75	0.239	0.239
			116.15	117.00	212628	0.85	0.463	0.463
			117.00	118.55	D519340	1.55	0.185	0.185
			118.55	119.55	212629	1.00	0.556	0.556
			119.55	120.55	212630	1.00	0.781	0.781
			120.55	121.50	D519341	0.95	0.147	0.147
			121.50	123.00	D519342	1.50	0.276	0.276
			123.00	124.50	D519343	1.50	0.120	0.120
			124.50	126.00	D519344	1.50	0.266	0.266
			126.00	127.50	D519345	1.50	0.047	0.047
			127.50	128.50	D519346	1.00	0.148	0.148
			128.50	130.00	212631	1.50	0.295	0.295
			130.00	131.50	212632	1.50	0.393	0.393
			131.50	133.00	212633	1.50	0.258	0.258
			133.00	134.20	212634	1.20	0.874	0.874
			134.20	135.00	D519347	0.80	1.280	1.280
			135.00	136.50	D519348	1.50	0.379	0.379
			136.50	138.30	D519349	1.80	0.051	0.051
138.30	144.80	SY PT POR <b>Syenite Lath Porphyry Intrusive 45°</b> Pink-brown dyke, carbonate-potassic rich with with elongate (albitized) laths parallel to banding axis at 45 to 50 degrees to CA, laths generally under 0.25cm diameter, very fine grained disseminated pyrite up to 0.5% contant. Chert-albite rich seams throughout.  128.5 to 134.0m: silicified-mineralized seams (brecciated hydrothermal)	138.30	139.80	212635	1.50	1.095	1.095
			139.80	141.30	212636	1.50	0.879	0.879
			141.30	142.80	212637	1.50	0.571	0.571
			142.80	144.80	212638	2.00	0.555	0.555

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
144.80	169.20	<p>with up to 0.5% to 1% pyrite, parallel banding at 4-45 and 70 degrees to CA, slightly altered (carbonate-sericite rich) to 150.7m depth. Void of sulfides.</p> <p>SY; POR</p> <p><b>Syenite; Porphyric</b></p> <p>Medium grained pink-red colour, carbonate rich upper contact and silic-chlor-seric. rich lower contact.</p>	144.80	146.00	D519351	1.20	0.013		0.013
144.80	145.50	<p>I2D; RUB</p> <p><b>Syenite; Banded</b></p> <p>Brecciated syenite and lath fragments parallel banding axis.</p>							
145.50	146.30	<p>I2D</p> <p><b>Syenite</b></p> <p>mafic minerals (planar amphibole/biotite mica).</p>	146.00	147.00	D519352	1.00	0.007		0.007
146.30	150.70	<p>I2D</p> <p><b>Syenite</b></p> <p>Carbonate rich seamlets, slight banding at 45 degrees to core axis.</p>	147.00	148.50	D519354	1.50	0.027		0.027
			148.50	150.00	D519355	1.50	0.070		0.070
			150.00	151.50	D519356	1.50	0.040		0.040
			151.50	153.00	D519357	1.50	0.370		0.370
			153.00	154.50	D519358	1.50	0.107		0.107
			154.50	156.00	D519359	1.50	0.360		0.360
			156.00	157.50	D519361	1.50	0.965		0.965
			157.50	159.00	D519362	1.50	0.828		0.828
			159.00	160.50	D519363	1.50	0.481		0.481
			160.50	162.00	D519364	1.50	0.502		0.502
			162.00	163.50	D519365	1.50	0.256		0.256
			163.50	165.00	D519366	1.50	0.174		0.174
			165.00	166.50	D519367	1.50	0.246		0.246
			166.50	168.00	D519368	1.50	0.315		0.315
166.60	169.20	<p>I2D</p> <p><b>Syenite 45°</b></p> <p>Cherty-siliceous seams parallel banding at 45 degrees to core axis with low disseminated pyrite.</p> <p>From 167.1 to 169.2m: increase in banding and chlorite content, finer grained, some coarse syenite fragments up to 6cm diameter.</p>	168.00	169.20	D519369	1.20	0.106		0.106
169.20	175.00	<p>SY; MNZ; POR</p>	169.20	170.50	212639	1.30	1.655		1.655



Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
175.00	187.00	<b>Syenite; Mineralized; Porphyric</b> Zone 2. Pink-grey-green color, siliceous rich quartz flooding, mafic (ultramafic rich lower contact) some fuchsite-carbonate rich seams, brecciated throughout, averaging up to 2.0 to 2.5% disseminated and seam pyrite in sections (ie-173.5m depth), some black cherty textured seams paralleling banding at 40 to 60 degrees to core axis.	170.50	172.00	212640	1.50	1.520	4.49	1.520		
			172.00	173.50	212641	1.50	1.955		1.955		
			173.50	175.00	212642	1.50	4.800		4.490		
		175.00	187.00	<b>Syenite; Massive rock</b> Massive and equigranular.	175.00	175.70	212643	0.70	0.063	4.49	0.063
					175.70	177.00	D519371	1.30	0.128		0.128
					177.00	178.50	D519372	1.50	0.373		0.373
					178.50	180.00	D519374	1.50	0.299		0.299
					180.00	181.50	D519375	1.50	0.666		0.666
175.00	177.00	I2D <b>Syenite</b> Slight banding and breccia fragments (decreasing with depth), non mineralized.	175.00	175.70	212643	0.70	0.063	4.49	0.063		
			175.70	177.00	D519371	1.30	0.128		0.128		
183.00	187.00	M15 <b>Skarn</b> Becoming increasingly fractured with feldspathic rich seams.	183.00	184.50	D519377	1.50	0.143	4.49	0.143		
			184.50	186.00	D519378	1.50	0.329		0.329		
			186.00	186.95	D519379	0.95	0.214		0.214		
			186.95	187.85	212647	0.90	0.986		0.986		
187.00	191.30	SY; MNZ; POR <b>Syenite; Mineralized; Porphyric</b> Zone 3. Siliceous rich banding at 40 to 45 degrees to core axis, albitized seams, some mineralized sections up to 4.0 to 5.0% pyrite seams and disseminations, quartz rich sections with chlorite-specular hematite hairline fractures.	187.85	188.95	212648	1.10	5.050	5.10	5.100		
			187.85	188.95	212648	1.10	5.050		5.100		
188.00	191.30	Py <b>Pyrite</b> Quartz vein with chlorite rich seams and mineralized breccia fragments, some specular hematite, central section less siliceous but well mineralized with pyrite seams, pyrite bleached by hydrothermal alteration.	188.95	189.95	212644	1.00	4.780	4.61	4.610		
			189.95	190.85	212645	0.90	12.900		12.900		
			190.85	191.45	212646	0.60	1.880		1.880		
188.00	191.30	VEI;;QzCl;;; <b>Vein Quartz Chlorite</b> Quartz vein with chlorite rich seams and mineralized breccia fragments, some specular hematite, central section less siliceous but well mineralized with pyrite seams, pyrite bleached	188.95	189.95	212644	1.00	4.780	4.61	4.610		
			189.95	190.85	212645	0.90	12.900		12.900		
			190.85	191.45	212646	0.60	1.880		1.880		

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
191.30	269.70	by hydrothermal alteration. GA; FIN <b>Gabbro 20°; Fine grains</b> Gabbro intrusive- fine grained, dark green colour, banded at 20 degrees to core axis along contacts but central portions with distinct coarser "speckled" appearance and epidote/chlorite rich.	191.45	192.50	D519380	1.05	0.492		0.492			
			192.50	193.50	D519381	1.00	0.085		0.085			
			193.50	195.00	D519382	1.50	0.005		0.005			
			195.00	196.50	D519383	1.50	<0.005		0.001			
			196.50	198.00	D519384	1.50	0.021		0.021			
			198.00	199.50	D519385	1.50	0.017		0.017			
			199.50	201.00	D519386	1.50	0.018		0.018			
			201.00	202.50	D519387	1.50	0.006		0.006			
			202.50	204.00	D519388	1.50	0.010		0.010			
			204.00	205.50	D519389	1.50	<0.005		0.001			
			205.50	207.00	D519391	1.50	<0.005		0.001			
			207.00	208.50	D519392	1.50	<0.005		0.001			
			208.50	210.00	D519394	1.50	<0.005		0.001			
			210.00	211.50	D519395	1.50	0.033		0.033			
		211.50	213.00	D519396	1.50	0.148		0.148				
191.30	212.70	Fc; RUB <b>Fuchsite; Banded</b> Finer grained with slight banding fabric.  From 196.5 to 198m: dark grey silica seams (crenulated), non mineralized with pervasive carbonate wisps, slight banding at 35 to 45 degrees to core axis (decreasing with depth), mafic rich (crenulated segregations) along siliceous seams, odd mineralized siliceous seam at 45 degrees to core axis with chlorite rich seams (ie 210.75m and 213.3 to 213.5m).										
			213.00	214.50	D519397	1.50	<0.005		0.001			
			214.50	216.00	D519398	1.50	<0.005		0.001			
			216.00	217.50	D519399	1.50	<0.005		0.001			
			217.50	219.00	D519401	1.50	<0.005		0.001			
			219.00	220.50	D519402	1.50	<0.005		0.001			
			220.50	222.00	D519403	1.50	<0.005		0.001			
			222.00	223.50	D519404	1.50	<0.005		0.001			
			223.50	225.00	D519405	1.50	<0.005		0.001			
			225.00	226.50	D519406	1.50	<0.005		0.001			
			212.70	269.70	I3G; MAS <b>Gabbro; Massive rock</b> More equigranular and massive gabbro, coarser grained with banding fabric decreasing with depth, sharp lower contact with syenite porphyry.							
						213.00	214.50	D519397	1.50	<0.005		0.001
						214.50	216.00	D519398	1.50	<0.005		0.001
						216.00	217.50	D519399	1.50	<0.005		0.001
217.50	219.00	D519401				1.50	<0.005		0.001			
219.00	220.50	D519402				1.50	<0.005		0.001			
220.50	222.00	D519403				1.50	<0.005		0.001			
222.00	223.50	D519404				1.50	<0.005		0.001			
223.50	225.00	D519405				1.50	<0.005		0.001			
225.00	226.50	D519406				1.50	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
End of hole at 297m.			276.00	277.50	D519445	1.50	0.005		0.005
			277.50	279.00	D519446	1.50	0.691		0.691
269.70	271.30	I2D; RUB <b>Syenite 45°; Banded</b> Banded and highly chloritized-sericitic harline fractures at 45 degrees to core axis, up to 2% fine disseminated magnetite crystals, up to 2% localized feldspar phenocrystals (zone, up to 1cm diameter, subeuhedral to sub-rounded).							
269.70	271.30	Chl; Ser <b>Chloritisation; Sericitisation</b> Banded and highly chloritized-sericitic harline fractures at 45 degrees to core axis, up to 2% fine disseminated magnetite crystals, up to 2% localized feldspar phenocrystals (zone, up to 1cm diameter, subeuhedral to sub-rounded).							
269.70	271.30	RUB <b>banded 45°</b> Banded and highly chloritized-sericitic harline fractures at 45 degrees to core axis, up to 2% fine disseminated magnetite crystals, up to 2% localized feldspar phenocrystals (zone, up to 1cm diameter, subeuhedral to sub-rounded).							
279.00	282.50	Car <b>Carbonatisation</b> Slight carbonate rich localized sections.	279.00	280.50	D519447	1.50	1.465		1.465
			280.50	282.00	D519448	1.50	0.142		0.142
			282.00	283.50	D519449	1.50	0.203		0.203
282.50	297.00	I2D; POR <b>Syenite; Porphyric</b> Coarser grained feldspar phenocrystals (up to 2.0cm diameter) and up to 5% content in localized sections, feldspathic and chlorite rich fractures at 50 degrees and 80 degrees to core axis.	283.50	285.00	D519451	1.50	0.046		0.046
			285.00	286.50	D519452	1.50	0.020		0.020
			286.50	288.00	D519454	1.50	<0.005		0.001
			288.00	289.50	D519455	1.50	0.028		0.028
			289.50	291.00	D519456	1.50	0.022		0.022
			291.00	292.50	D519457	1.50	0.116		0.116
			292.50	294.00	D519458	1.50	0.050		0.050
			294.00	295.50	D519459	1.50	<0.005		0.001
			295.50	297.00	D519460	1.50	<0.005		0.001

## Corporation Minière Osisko Div. Exploration

297.00

Fin du sondage

Nombre d'échantillons : 206

Nombre d'échantillons QAQC : 20

Longueur totale échantillonnée : 294.60

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
19.50	19.50	213515	O6Pc	0.00	1.565	1.565
25.50	25.50	213520	m	0.00	<0.005	0.001
46.50	46.50	213535	O54Pa	0.00	2.960	2.960
52.50	52.50	213540	m	0.00	<0.005	0.001
73.50	73.50	212600	m	0.00	<0.005	0.001
144.80	146.00	D519350	O52Pb	1.20	0.291	0.291
146.00	147.00	D519353	D519352	1.00	0.006	0.006
156.00	157.50	D519360	m	1.50	0.006	0.006
175.70	177.00	D519370	O54Pa	1.30	2.940	2.940
177.00	178.50	D519373	D519372	1.50	0.400	0.400
205.50	207.00	D519390	O61d	1.50	4.810	4.810
207.00	208.50	D519393	D519392	1.50	<0.005	0.001
217.50	219.00	D519400	m	1.50	<0.005	0.001
231.00	232.50	D519410	O50Pb	1.50	0.850	0.850
232.50	234.00	D519413	D519412	1.50	<0.005	0.001
258.00	259.50	D519430	O52Pb	1.50	0.302	0.302
259.50	261.00	D519433	D519432	1.50	0.007	0.007
270.00	271.50	D519440	m	1.50	0.005	0.005
283.50	285.00	D519450	O54Pa	1.50	3.150	3.150
285.00	286.50	D519453	D519452	1.50	0.033	0.033

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-80	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multidrill	Lot :	
Décrit par : Genevieve Carignan	Du : 2009-10-23	Date de description : 2009-10-26
	Au : 2009-10-26	

Collet

Azimut : 155.45°  
 Plongée : -46.80°  
 Longueur : 182.00 m

UTM

Est	630 123.4
Nord	5 374 301.8
Élévation	295.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	30.00	169.50°	-45.50°	Non
Reflex	60.00	169.50°	-44.70°	Non
Reflex	90.00	171.00°	-43.60°	Non
Reflex	120.00	5.50°	-46.60°	Oui
Reflex	150.00	169.30°	-41.40°	Non
Reflex	180.00	159.90°	-40.00°	Oui

Type	Profondeur	Azimut	Plongée	Invalide

Description

GPS Datum NAD83, UTM Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	1.50	MT <b>Casing</b> Casing.							
1.50	49.50	SY POR <b>Syenite Porphyry Intrusive</b> Red to green-greyish fine to medium grained syenite porphyry intrusive. Less than 5% chloritized/albitized Fp phenos (~1cm). Heterogenous, loc brecciated (with albite filling the fractures) and loc foliated (light) @ 40-50 TCA. 1% Smokey Qtz veins (~1cm) @ 30-40TCA. Moderatly magnetic.  Light to moderate chloritisation making the light foliation @ 40-50TCA. Albitisation filling the fractures and in veins with white Qtz @ 50-60TCA. Light pervasive silicification. Weathering in the fractures and moderate between 1.5 and 4.1m.  Traces to locally 1% of disseminated fine pyrite.  core grinded and not recovered 1.5m to 4m	1.50	2.30	228956	0.80	2.970		2.970
1.50	2.70	BC <b>Broken core</b> Broken core and weathering.							
2.70	4.10	CNR <b>Core Not recovered</b> CNR	3.50	4.50	228957	1.00	1.925		1.925
			4.50	6.00	207994	1.50	2.320		2.320
			6.00	7.50	207996	1.50	1.780		1.780
			7.50	9.00	207997	1.50	1.520		1.520
			9.00	10.50	207998	1.50	0.799		0.799
			10.50	12.00	207999	1.50	0.229		0.229
			12.00	13.50	213001	1.50	0.654		0.654
			13.50	15.00	213002	1.50	0.721		0.721
14.10	18.50	Py04 <b>Pyrite 04%</b> 3-5% very fine (loc cubic) disseminated pyrite and associated to Smokey Qtz veins.	15.00	16.50	213003	1.50	0.822		0.822
			16.50	18.00	213004	1.50	1.545		1.545
			18.00	19.50	213005	1.50	1.170		1.170
			19.50	21.00	213006	1.50	1.095		1.095



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
22.20	23.90	Wea	21.00	22.50	213007	1.50	0.893	2.80	0.893
		<b>Weathering (Incl. Saprolitic alter.)</b> Moderate weathering in fractures.	22.50	24.00	213008	1.50	0.896		0.896
			24.00	25.50	213009	1.50	0.435		0.435
			25.50	27.00	213010	1.50	0.230		0.230
			27.00	28.50	213011	1.50	0.390		0.390
			28.50	30.00	213012	1.50	0.719		0.719
			30.00	31.50	213013	1.50	2.280		2.280
30.10	30.80	Py03							
		<b>Pyrite 03%</b> 2-3% very fine (loc cubic) disseminated pyrite.							
30.80	35.00	Py05							
		<b>Pyrite 05%</b> 4-7% very fine disseminated pyrite.							
31.30	33.70	Sil	31.50	33.00	213014	1.50	3.040	2.80	2.800
		<b>Silicification</b> Intense pervasive silicification.	33.00	34.50	213016	1.50	2.610		2.610
			34.50	36.00	213017	1.50	0.524		0.524
			36.00	37.50	213018	1.50	0.115		0.115
			37.50	39.00	213019	1.50	0.196		0.196
			39.00	40.50	213020	1.50	0.269		0.269
			40.50	42.00	213021	1.50	0.116		0.116
			42.00	43.50	213022	1.50	0.587		0.587
42.55	42.70	Py03	43.50	45.00	213023	1.50	1.275		1.275
		<b>Pyrite 03%</b> 2-4% very fine disseminated pyrite associated with Smokey Qtz veins.	45.00	46.50	213024	1.50	0.095		0.095
			46.50	48.00	213025	1.50	0.079		0.079
			48.00	49.50	213026	1.50	0.066		0.066
49.50	165.80	SY POR	49.50	51.00	213027	1.50	0.029		0.029
		<b>Syenite Porphyry Intrusive</b> Dark purple to purple-grey, fine to medium grained syenite porphyry intrusive. 20-25% of Fp phenos (1mm to 1cm). Homogenous, mostly massive and magnetic. 1-2% Qtz-Ca veins @ 30-50TCA. Upper contact is gradual on ~2m. Loc brecciated. 1% Smokey Qtz veins @ 30-50TCA with pyrite in the vein walls. Lower contact sharp @ 45TCA.  Light pervasive silicification. Light to moderate chloritisation mostly as	51.00	52.50	213028	1.50	0.012		0.012
			52.50	54.00	213029	1.50	0.288		0.288
			54.00	55.50	213030	1.50	0.135		0.135
			55.50	57.00	213031	1.50	0.815		0.815
			57.00	58.50	213032	1.50	0.420		0.420
			58.50	60.00	213033	1.50	0.246		0.246
			60.00	61.50	213034	1.50	0.232		0.232
			61.50	63.00	213035	1.50	0.200		0.200

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
		veinlets and stringers.	63.00	64.50	213037	1.50		0.173		0.173
			64.50	66.00	213038	1.50		1.165		1.165
		Traces to 1% fine disseminated pyrite.	66.00	67.50	213039	1.50		0.433		0.433
			67.50	69.00	213040	1.50		0.225		0.225
			69.00	70.50	213041	1.50		0.087		0.087
			70.50	72.00	213042	1.50		1.025		1.025
			72.00	73.50	213043	1.50		0.230		0.230
			73.50	75.00	213044	1.50		0.489		0.489
			75.00	76.50	213045	1.50		0.211		0.211
			76.50	78.00	213046	1.50		0.176		0.176
			78.00	79.50	213047	1.50		0.235		0.235
			79.50	81.00	213048	1.50		0.091		0.091
			81.00	82.50	213049	1.50		0.149		0.149
81.50	82.50	Chl <b>Chloritisation</b> Moderate to high pervasive chloritisation.								
82.40	82.50	BRE <b>Breccia</b> Qtz-Ca breccia. Probably a brecciated Qtz-Ca vein. With 2-3% very fine disseminated pyrite mostly along vein walls.	82.50	84.00	213051	1.50		0.072		0.072
			84.00	85.50	213052	1.50		0.029		0.029
			85.50	87.00	213053	1.50		0.048		0.048
			87.00	88.50	213054	1.50		0.039		0.039
			88.50	90.00	213056	1.50		0.055		0.055
			90.00	91.50	213057	1.50		0.080		0.080
			91.50	93.00	213058	1.50		0.123		0.123
			93.00	94.50	213059	1.50		0.044		0.044
			94.50	96.00	213060	1.50		0.020		0.020
			96.00	97.50	213061	1.50		0.692		0.692
			97.50	99.00	213062	1.50		0.219		0.219
			99.00	100.50	213063	1.50		1.575		1.575
99.90	100.30	Py03 <b>Pyrite 03%</b> 2-4% very fine (loc cubic) disseminated pyrite.	100.50	102.00	213064	1.50		0.406		0.406
			102.00	103.50	213065	1.50		1.040		1.040
			103.50	105.00	213066	1.50		0.043		0.043
			105.00	106.50	213067	1.50		0.071		0.071
			106.50	108.00	213068	1.50		0.188		0.188
			108.00	109.50	213069	1.50		0.030		0.030

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
110.00	156.25	Chl <b>Chloritisation</b> Moderate pervasive chloritisation.	109.50	111.00	213070	1.50	0.011		0.011
			111.00	112.50	213071	1.50	<0.005		0.001
			112.50	114.00	213072	1.50	0.039		0.039
			114.00	115.50	213073	1.50	0.905		0.905
			115.50	117.00	213074	1.50	0.031		0.031
			117.00	118.50	213076	1.50	0.894		0.894
118.10	118.60	Py03 <b>Pyrite 03%</b> 2-4% very fine to fine disseminated pyrite.	118.50	120.00	213077	1.50	0.032		0.032
			120.00	121.50	213078	1.50	0.260		0.260
			121.50	123.00	213079	1.50	0.335		0.335
			123.00	124.50	213081	1.50	0.090		0.090
			124.50	126.00	213082	1.50	0.837		0.837
			126.00	127.50	213083	1.50	0.125		0.125
			127.50	129.00	213084	1.50	0.063		0.063
			129.00	130.50	213085	1.50	0.142		0.142
			130.50	132.00	213086	1.50	0.664		0.664
			132.00	133.50	213087	1.50	0.028		0.028
			133.50	135.00	213088	1.50	0.148		0.148
			135.00	136.50	213089	1.50	0.223		0.223
			136.50	138.00	213090	1.50	0.191		0.191
			138.00	139.50	213091	1.50	0.238		0.238
			139.50	141.00	213092	1.50	0.402		0.402
			141.00	142.50	213093	1.50	0.270		0.270
			142.50	144.00	213094	1.50	0.813		0.813
			144.00	145.50	213096	1.50	0.021		0.021
145.50	147.00	213097	1.50	1.415		1.415			
147.00	148.50	213098	1.50	0.339		0.339			
148.50	150.00	213099	1.50	0.007		0.007			
150.00	151.50	213101	1.50	0.011		0.011			
151.50	153.00	213102	1.50	0.168		0.168			
153.00	154.50	213103	1.50	0.008		0.008			
154.50	156.00	213104	1.50	0.383		0.383			
155.50	158.30	BRE <b>Breccia</b> Brecciated syenite with albite+quartz filling the fractures. Small	156.00	157.50	213105	1.50	0.616		0.616

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
156.25	157.60	fragments (1cm). Sil <b>Silicification</b> Moderate silicification. Pervasive and in thin (2mm) veinlets @ 40TCA.							
156.25	157.60	Py03 <b>Pyrite 03%</b> 2-4% very fine (loc cubic) disseminated pyrite.	157.50	159.00	213106	1.50	0.312		0.312
157.60	165.80	Chl <b>Chloritisation</b> Moderate pervasive chloritisation.	159.00	160.50	213107	1.50	0.128		0.128
			160.50	162.00	213108	1.50	0.092		0.092
			162.00	163.50	213109	1.50	0.286		0.286
			163.50	165.00	213110	1.50	0.503		0.503
			165.00	166.50	213111	1.50	0.653		0.653
165.80	182.00	BA <b>Mafic Meta-Volcanic</b> Dark green to green aphanitic to fine grained mafic metavolcanic. Light to moderate foliation @ 50-60TCA. Locally brecciated. 2-3% white Quartz veins and injections. 2-3% Qtz+-Ca veins (~5mm) @ 30TCA. Upper contact sharp @ 45TCA.  Moderate chloritisation (dark green chlorite) making the foliation.  1% very fine to fine disseminated pyrite (loc cubic).	166.50	168.00	213112	1.50	0.153		0.153
			168.00	169.50	213113	1.50	0.118		0.118
			169.50	171.00	213114	1.50	0.011		0.011
			171.00	172.50	213116	1.50	0.007		0.007
			172.50	174.00	213117	1.50	0.007		0.007
			174.00	175.50	213118	1.50	0.030		0.030
			175.50	177.00	213119	1.50	0.174		0.174
			177.00	178.50	213120	1.50	0.343		0.343
			178.50	180.00	213121	1.50	0.187		0.187
		End of hole; 182m							
179.30	181.30	STW;30%;Qz;;;Py01; <b>Stockwerk 30% Quartz Pyrite01%</b> White Quartz stockwerk with tr to 1% pyrite.	180.00	181.00	213122	1.00	0.130		0.130
			181.00	182.00	213123	1.00	0.144		0.144
181.60	181.85	BC <b>Broken core</b> Broken core.							
182.00	Fin du sondage Nombre d'échantillons : 121 Nombre d'échantillons QAQC : 11 Longueur totale échantillonnée : 179.30								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.50	6.00	207995	O53Pb	1.50	0.668	0.668
10.50	12.00	208000	m	1.50	0.007	0.007
31.50	33.00	213015	O15Pa	1.50	1.030	1.030
61.50	63.00	213036	O6Pc	1.50	1.565	1.565
81.00	82.50	213050	m	1.50	0.005	0.005
87.00	88.50	213055	O54Pa	1.50	3.010	3.050
115.50	117.00	213075	O50Pb	1.50	0.902	0.902
121.50	123.00	213080	m	1.50	0.006	0.006
142.50	144.00	213095	O61d	1.50	5.110	5.160
150.00	151.50	213100	m	1.50	0.005	0.005
169.50	171.00	213115	O53Pb	1.50	0.618	0.618

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-81

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie mine

Foré par : Multidrill

Lot :

Décrit par : Genevieve Carignan

Du : 2009-10-26

Date de description : 2009-10-28

Au : 2009-10-27

Collet

UTM

Azimut : 125.04°

Plongée : -46.20°

Longueur : 110.00 m

Est 629 962.9

Nord 5 374 471.3

Élévation 282.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	135.13°	-45.52°	Non
Reflex	42.00	137.88°	-45.73°	Non
Reflex	45.00	138.77°	-45.56°	Non
Reflex	48.00	136.03°	-45.25°	Non
Reflex	51.00	139.03°	-45.23°	Non
Reflex	54.00	139.08°	-45.05°	Non
Reflex	57.00	136.81°	-45.04°	Non
Reflex	60.00	139.88°	-44.99°	Non
Reflex	63.00	138.01°	-44.96°	Non
Reflex	66.00	137.71°	-44.76°	Non
Reflex	69.00	139.60°	-44.97°	Non
Reflex	72.00	138.62°	-44.71°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	142.00°	-44.58°	Oui
Reflex	78.00	140.54°	-44.64°	Non
Reflex	81.00	141.93°	-44.25°	Non
Reflex	84.00	138.85°	-44.24°	Non
Reflex	87.00	139.58°	-44.19°	Non
Reflex	90.00	140.18°	-43.67°	Non
Reflex	93.00	141.10°	-43.67°	Non
Reflex	96.00	140.46°	-43.52°	Non
Reflex	99.00	139.36°	-43.55°	Non
Reflex	102.00	139.19°	-43.64°	Non
Reflex	105.00	139.53°	-43.57°	Non
Reflex	108.00	142.89°	-43.36°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Hit drift @ 110m.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	33.00	MT <b>Casing</b> Casing.							
33.00	84.50	BA <b>Mafic Meta-Volcanic</b> Dark green to medium green fine to medium grained (loc coarse grained) mafic metavolcanic. Light to moderate foliation @ 40-50TCA but locally massive. 2-3% Ca+-Qtz veins @ 50-60TCA and injections. Zone with up to 10% (mean is between 5-8%) rounded calcite amygdules (2-3mm, up to 1cm). Locally Broken core.  Light pervasive chloritisation and light carbonatisation. Locally light to moderate bleaching. Locally light sericitisation.  Tr-1% very fine to fine disseminated pyrite.	33.00	34.50	213124	1.50	<0.005		0.001
			34.50	36.00	213125	1.50	<0.005		0.001
			36.00	37.50	213126	1.50	<0.005		0.001
			37.50	39.00	213127	1.50	<0.005		0.001
			39.00	40.50	213128	1.50	0.017		0.017
40.00	40.40	BRE; BC <b>Breccia ; Broken core</b> Broken core. Breccia (fragments 2-5cm) with 2% fine pyrite.	40.50	42.00	213129	1.50	<0.005		0.001
			42.00	43.50	213131	1.50	<0.005		0.001
			43.50	45.00	213132	1.50	<0.005		0.001
			45.00	46.50	213133	1.50	<0.005		0.001
			46.50	48.00	213134	1.50	0.009		0.009
47.10	47.45	Py06 <b>Pyrite 06%</b> 5-7% fine pyrite. Disseminated, in clusters and in stringers.	48.00	49.50	213136	1.50	0.005		0.005
			49.50	51.00	213137	1.50	<0.005		0.001
			51.00	52.50	213138	1.50	<0.005		0.001
			52.50	54.00	213139	1.50	<0.005		0.001
			54.00	55.50	213140	1.50	<0.005		0.001
55.15	71.30	V2 <b>Intermediate Volcanic (Flow)</b> Medium green to light green-beige aphanitic to fine grained intermediate metavolcanic. Light to moderate foliation @ 30-40TCA. 2-3% Ca veins @ 30-40TCA and injections. Loc 2-3% Ca amygdules (<1cm). Upper contact sharp @ 30TCA and lower contact sharp @ 45TCA.  Light to moderate sericitisation and chloritisation. Moderate carbonatisation.  Tr-1% very fine to fine disseminated pyrite.	55.50	57.00	213141	1.50	<0.005		0.001
			57.00	58.50	213142	1.50	0.013		0.013
58.20	58.50	BC	58.50	60.00	213143	1.50	0.012		0.012

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Broken core</b>	60.00	61.50	213144	1.50		0.005
		Broken core.	61.50	63.00	213145	1.50		0.015
			63.00	64.50	213146	1.50		0.014
			64.50	66.00	213147	1.50		<0.005
			66.00	67.50	213148	1.50		<0.005
			67.50	69.00	213149	1.50		<0.005
			69.00	70.50	213151	1.50		<0.005
			70.50	72.00	213152	1.50		0.005
			72.00	73.50	213153	1.50		<0.005
			73.50	75.00	213154	1.50		0.005
			75.00	76.50	213156	1.50		0.005
			76.50	78.00	213157	1.50		<0.005
			78.00	79.50	213158	1.50		<0.005
			79.50	81.00	213159	1.50		0.005
			81.00	82.50	213160	1.50		0.174
			82.50	84.00	213161	1.50		0.094
			84.00	85.50	213162	1.50		1.390
84.50	110.00	SY POR	85.50	87.00	213163	1.50		0.515
		<b>Syenite Porphyry Intrusive</b>						
		Purple-grey fine to medium grained syenite porphyry intrusive. 1-2% altered Fp phenos. Mostly massive but foliated @ 40-50TCA where chloritized. 1-2% Qtz+-Ca @ 40-50TCA. Tr smokey Qtz veins @ 60TCA. Upper contact sharp @ 30TCA.						
		Light chloritisation making the foliation (+fine stringers). Light pervasive silicification.						
		End of hole: 110m Hit drift.						
86.70	100.00	Sil; Car; Ser						
		<b>Silicification; Carbonatisation; Sericisation</b>						
		Intense pervasive silicification with light carbonatisation as calcite veins @ 40-50TCA, injections and pervasive. Light sericisation. Upper contact is gradual.						
86.70	100.00	BRE						
		<b>Breccia</b>						
		Lightly brecciated.						



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
86.70	100.00	Py06 <b>Pyrite 06%</b> 6-8% (up to 10%) very fine pyrite. Disseminated and as fine stringers. Associated with the silicification.  North or RW Zone.	87.00	88.50	213164	1.50	0.383		0.383
			88.50	90.00	213165	1.50	2.470		2.470
			90.00	91.50	213166	1.50	4.930	5.04	5.040
			91.50	93.00	213167	1.50	4.350	4.41	4.410
			93.00	94.50	213168	1.50	3.540	3.66	3.660
			94.50	96.00	213169	1.50	5.040	5.03	5.030
			96.00	97.50	213171	1.50	3.200	3.24	3.240
			97.50	99.00	213172	1.50	3.730	3.73	3.730
			99.00	100.50	213173	1.50	2.330		2.330
			100.50	102.00	213174	1.50	0.554		0.554
			102.00	103.50	213176	1.50	0.243		0.243
			103.50	105.00	213177	1.50	0.286		0.286
			105.00	106.50	213178	1.50	0.354		0.354
			106.50	108.00	213179	1.50	0.483		0.483
108.00	109.00	213180	1.00	0.282		0.282			
109.00	110.00	213181	1.00	0.088		0.088			
109.90	110.00	UW <b>Underground Workings</b> Hit drift @ 110m.							
110.00	Fin du sondage Nombre d'échantillons : 52 Nombre d'échantillons QAQC : 6 Longueur totale échantillonnée : 77.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
40.50	42.00	213130	m	1.50	<0.005	0.001
46.50	48.00	213135	O15Pa	1.50	1.055	1.055
67.50	69.00	213150	m	1.50	<0.005	0.001
73.50	75.00	213155	O6Pc	1.50	1.640	1.640
94.50	96.00	213170	m	1.50	0.010	0.010
99.00	100.50	213175	O54Pa	1.50	2.920	2.920

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-82	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie mine
Foré par : Multidrill	Lot :	
Décrit par : Genevieve Carignan	Du : 2009-10-27	Date de description : 2009-10-29
	Au : 2009-10-28	

Collet

Azimut : 128.66°  
 Plongée : -45.50°  
 Longueur : 97.00 m

UTM

Est	629 918.1
Nord	5 374 453.9
Élévation	281.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	60.00	144.30°	-43.40°	Non
Reflex	90.00	147.90°	-42.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

GPS Datum NAD83, UTM Zone 17.

57.5m-58.6m lost core

Hit drift @ 97m.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	30.00	MT <b>Casing</b> Casing.							
30.00	81.50	BA <b>Mafic Meta-Volcanic</b> Dark green to medium green fine grained to locally medium grained mafic metavolcanic. Light to medium foliation @ 50-60TCA. Zones with 5% (up to 10%) rounded calcite amygdules (2mm to 1cm) and 1-2% grey Qtz amygdules (2-3mm). 1-2% calcite veinlets @ 40-60TCA. Loccally brecciated. Generally homogenous and non magnetic.  Light pervasive chloritisation and light carbonatisation. Locally light to moderate bleaching. Locally light sericitisation.  Tr-1% (loc 3-4%) fine disseminated pyrite (locally in the amygdules).	30.00	31.50	213182	1.50	<0.005		0.001
			31.50	33.00	213183	1.50	0.005		0.005
			33.00	34.50	213184	1.50	<0.005		0.001
			34.50	36.00	213185	1.50	<0.005		0.001
			36.00	37.50	213186	1.50	<0.005		0.001
			37.50	39.00	213187	1.50	<0.005		0.001
			39.00	40.50	213188	1.50	<0.005		0.001
			40.50	42.00	213189	1.50	<0.005		0.001
			42.00	43.50	213191	1.50	<0.005		0.001
			43.50	45.00	213192	1.50	0.007		0.007
44.70	45.40	Py04 <b>Pyrite 04%</b> 3-5% pyrite. Mostly in Ca amygdules but also disseminated.	45.00	46.50	213193	1.50	<0.005		0.001
45.30	81.50	Blch <b>Bleaching</b> Moderate bleaching.	46.50	48.00	213194	1.50	0.007		0.007
			48.00	49.50	213196	1.50	<0.005		0.001
			49.50	51.00	213197	1.50	0.006		0.006
50.50	57.40	BC <b>Broken core</b> 30% broken core and light weathering on the blocks.	51.00	52.50	213198	1.50	0.009		0.009
			52.50	54.00	213199	1.50	<0.005		0.001
			54.00	55.50	213200	1.50	0.008		0.008
			55.50	57.40	213201	1.90	0.007		0.007
57.40	58.50	CNR <b>Core Not recovered</b> Lost core between 57.4-58.5m	58.60	60.00	213202	1.40	0.010		0.010
			60.00	61.50	213203	1.50	<0.005		0.001
			61.50	63.00	213204	1.50	<0.005		0.001
			63.00	64.50	213205	1.50	<0.005		0.001
			64.50	66.00	213206	1.50	<0.005		0.001
			66.00	67.50	213207	1.50	<0.005		0.001
			67.50	69.00	213208	1.50	<0.005		0.001
			69.00	70.50	213209	1.50	0.005		0.005
			70.50	72.00	213210	1.50	<0.005		0.001
			72.00	73.50	213211	1.50	<0.005		0.001
			73.50	75.00	213212	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
81.50	94.90	<p>SY; BSF</p> <p><b>Syenite; Breccia Silicified zone</b></p> <p>Grey-greenish silicified-sericitized mineralized lightly brecciated syenite. 1-2% very altered fp phenos (~1cm). 1-2% Qtz-Ca veins (5mm to 1cm) @ 40-50TCA. Upper contact sharp @ 55TCA and lower contact is broken.</p> <p>Intense pervasive grey silicification and pervasive sericitisation. Light chloritisation in stringers. Moderate carbonatisation in the matrix.</p> <p>4-7% very fine pyrite (loc cubic). Disseminated and in fine stringers.</p>	75.00	76.50	213213	1.50	<0.005		0.001
			76.50	78.00	213214	1.50	<0.005		0.001
			78.00	79.50	213216	1.50	0.008		0.008
			79.50	81.00	213217	1.50	0.006		0.006
			81.00	81.50	213218	0.50	0.008		0.008
81.50	84.20	<p>Ser</p> <p><b>Sericitisation</b></p> <p>Intense pervasive sericitisation. Lower contact is gradual.</p>							
81.50	94.90	<p>Py05</p> <p><b>Pyrite 05%</b></p> <p>4-7% very fine pyrite. Disseminated and in fine stringers.</p>	81.50	82.50	213219	1.00	0.728		0.728
			82.50	84.00	213220	1.50	2.030		2.030
			84.00	85.50	213221	1.50	1.070		1.070
			85.50	87.00	213222	1.50	1.125		1.125
			87.00	88.50	213223	1.50	0.805		0.805
			88.50	90.00	213224	1.50	1.355		1.355
			90.00	91.50	213225	1.50	0.911		0.911
			91.50	93.00	213226	1.50	2.050		2.050
93.00	94.90	213227	1.90	0.015		0.015			
94.80	94.90	<p>BC</p> <p><b>Broken core</b></p> <p>10cm broken core at the upper contact of the mafic metavolcanic.</p>							
94.90	97.00	<p>BA</p> <p><b>Mafic Meta-Volcanic</b></p> <p>Dark green to medium green fine grained to locally medium grained</p>	94.90	96.00	213228	1.10	0.011		0.011
			96.00	97.00	213229	1.00	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description		Analyse							
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
96.90	97.00								
<p>mafic metavolcanic. Light foliation @ 50-60TCA. Zones with 3% rounded calcite amygdules (2mm to 1cm). 1-2% calcite injections. Locally brecciated. Homogenous and non magnetic.</p> <p>Light pervasive chloritisation and light carbonatisation.</p> <p>Tr-1% fine disseminated pyrite (locally in the amygdules).</p> <p>Hit drift @ 97m.</p> <p>UW</p> <p><b>Underground Workings</b></p> <p>Hit drift @ 97m.</p>									
97.00	<p>Fin du sondage</p> <p>Nombre d'échantillons : 45</p> <p>Nombre d'échantillons QAQC : 3</p> <p>Longueur totale échantillonnée : 65.80</p>								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
40.50	42.00	213190	m	1.50	<0.005	0.001
46.50	48.00	213195	O50Pb	1.50	0.866	0.866
76.50	78.00	213215	O61d	1.50	5.070	4.740

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-83

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail : Beattie mine

Foré par : Multidrill

Lot :

Décrit par : Genevieve Carignan

Du : 2009-10-28

Date de description : 2009-10-30

Au : 2009-10-30

Collet

UTM

Azimut : 121.90°

Plongée : -45.40°

Longueur : 189.00 m

Est 630 000.7

Nord 5 374 493.1

Élévation 280.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	139.64°	-43.32°	Non
Reflex	42.00	137.44°	-43.40°	Non
Reflex	45.00	134.70°	-43.43°	Oui
Reflex	48.00	136.86°	-43.54°	Non
Reflex	51.00	137.81°	-43.15°	Non
Reflex	54.00	132.77°	-43.35°	Non
Reflex	57.00	134.67°	-43.28°	Non
Reflex	60.00	132.34°	-42.90°	Non
Reflex	63.00	135.64°	-42.74°	Non
Reflex	66.00	136.10°	-42.98°	Non
Reflex	69.00	137.63°	-42.85°	Non
Reflex	72.00	135.62°	-42.42°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	137.66°	-42.20°	Non
Reflex	78.00	139.25°	-42.13°	Non
Reflex	81.00	136.30°	-42.12°	Oui
Reflex	84.00	139.09°	-42.02°	Non
Reflex	87.00	138.46°	-42.29°	Non
Reflex	90.00	136.14°	-42.23°	Non
Reflex	93.00	136.67°	-42.15°	Non
Reflex	96.00	137.70°	-42.06°	Non
Reflex	99.00	135.04°	-41.60°	Non
Reflex	102.00	138.00°	-41.86°	Oui
Reflex	105.00	137.73°	-41.55°	Oui
Reflex	108.00	135.38°	-41.49°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	36.10	MT <b>Casing</b> Casing.							
36.10	189.00	SY POR <b>Syenite Porphyry Intrusive</b> Dark purple to greenish-greyish purple fine grained syenite porphyry intrusive. 8-10% (up to 15%) Fp phenos (2mm to 1cm). Phenos are locally altered in chlorite. Syenite is mostly homogenous and moderately magnetic. 3-4% Qtz-Alb+-Ca veins @ 40-50TCA.  Light to loc moderate pervasive chloritisation and in fine stringers. Local weathering in the fractures. Light carbonatisation and albitisation in the Qtz-Alb+-Ca veins. overall Tr very fine disseminated pyrite.  loc. mod-highly silicified and loc. brecciated with Py concentrations ranging from Tr-5%  EOH@189m	36.10	37.50	213230	1.40	0.249		0.249
36.10	37.00	BC <b>Broken core</b> Broken core. Mostly blocks of 5-10cm.							
37.00	38.00	CNR <b>Core Not recovered</b> Lost 1m of core.	37.50	39.00	213231	1.50	0.012		0.012
38.00	38.60	BC <b>Broken core</b> Broken core.	39.00	40.50	213232	1.50	0.517		0.517
			40.50	42.00	213233	1.50	0.300		0.300
			42.00	43.50	213234	1.50	0.038		0.038
			43.50	45.00	213235	1.50	0.041		0.041
43.80	46.80	Chl <b>Chloritisation</b> Moderate pervasive chloritisation.	45.00	46.50	213236	1.50	0.111		0.111
			46.50	48.00	213237	1.50	0.087		0.087
			48.00	49.50	213238	1.50	0.105		0.105
			49.50	51.00	213239	1.50	0.161		0.161
			51.00	52.50	213241	1.50	0.030		0.030
			52.50	54.00	213242	1.50	0.019		0.019
			54.00	55.50	213243	1.50	0.013		0.013
			55.50	57.00	213244	1.50	0.086		0.086

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			57.00	58.50	213245	1.50	0.037		0.037
			58.50	60.00	213246	1.50	0.096		0.096
58.80	61.20	Sil; Chl <b>Silicification; Chloritisation</b> Moderate pervasive silicification with moderate chloritisation (pervasive and as stringers).							
58.80	61.20	Py02 <b>Pyrite 02%</b> 1-3% very fine disseminated pyrite.	60.00	61.50	213247	1.50	0.094		0.094
			61.50	63.00	213248	1.50	0.133		0.133
			63.00	64.50	213249	1.50	0.641		0.641
63.80	68.20	Py03 <b>Pyrite 03%</b> mod-highly silicified and partially brecciated, diss. to dendritic Py loc. in stringers, loc. +/++ chl&seric							
64.00	65.50	Chl; Ser <b>Chloritisation; Sericitisation</b> grayish green to light green, +/++ Chl&seric. rock	64.50	66.00	213250	1.50	0.597		0.597
			66.00	67.50	213251	1.50	0.111		0.111
			67.50	69.00	213252	1.50	0.069		0.069
			69.00	70.50	213253	1.50	0.084		0.084
			70.50	72.00	213254	1.50	0.986		0.986
			72.00	73.50	213255	1.50	0.171		0.171
			73.50	75.00	213256	1.50	0.214		0.214
			75.00	76.50	213257	1.50	0.049		0.049
			76.50	78.00	213258	1.50	0.072		0.072
78.00	81.00	Oxy <b>Oxydation</b> rusty brown to reddish brown loc. +/++ oxidized interval, partially fractured, random chlo. filled microfractures and 1-2% Qtz-Carb injections@80TCA(less than cm sized)	78.00	79.50	213259	1.50	0.365		0.365
79.50	81.00	FRC <b>Fractured</b> 1-5% fractured core	79.50	81.00	213261	1.50	0.025		0.025
			81.00	82.50	213262	1.50	0.005		0.005
			82.50	84.00	213263	1.50	0.057		0.057
			84.00	85.50	213264	1.50	0.018		0.018
			85.50	87.00	213265	1.50	0.712		0.712
			87.00	88.50	213266	1.50	0.232		0.232
			88.50	90.00	213267	1.50	0.110		0.110
			90.00	91.50	213268	1.50	0.036		0.036

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
97.05	116.30	Py05 <b>Pyrite 05%</b> mod-highly silicification with local hydro-brecciation, finely disseminated Py to dendritic with random cubic Py loc., rock is brownish light to dark gray to wine red., 3-5% Qtz-Carb injections loc. +/++ alb and/or K-altered @~50TCA(up to 10cm thick loc.) associated loc. to chl patchjes or microfractures, Py decrease to 1-3% downward the lower CT	91.50	93.00	213269	1.50	0.049		0.049
			93.00	94.50	213271	1.50	0.150		0.150
			94.50	96.00	213272	1.50	2.160		2.160
			96.00	97.50	213273	1.50	1.210		1.210
			97.50	99.00	213274	1.50	1.010		1.010
99.00	102.00	Car <b>Carbonatisation</b> red brick to pink salmon alteration patches	99.00	100.50	213275	1.50	2.810	4.36 5.72	2.810
			100.50	102.00	213276	1.50	2.830		2.830
			102.00	103.50	213277	1.50	4.790		4.360
			103.50	105.00	213278	1.50	5.840		5.720
			105.00	106.50	213279	1.50	2.680		2.680
			106.50	108.00	213281	1.50	2.730		2.730
			108.00	109.50	213282	1.50	1.035		1.035
			109.50	111.00	213283	1.50	2.380		2.380
			111.00	112.50	213284	1.50	2.950		2.950
			112.50	114.00	213285	1.50	0.700		0.700
			114.00	115.50	213286	1.50	0.821		0.821
			115.50	117.00	213287	1.50	1.380		1.380
117.00	123.00	FRC <b>Fractured</b> 1-3% fractured core	117.00	118.50	213288	1.50	0.513		0.513
			118.50	120.00	213289	1.50	0.963		0.963
119.65	123.45	Py03 <b>Pyrite 03%</b> dark gray to greenish gray, 1-3% finely diss. Py, mod-highly silicification, loc. hydro-brecciated	120.00	121.50	213291	1.50	1.950		1.950
			121.50	123.00	213292	1.50	1.590		1.590
			123.00	124.50	213293	1.50	1.100		1.100
			124.50	126.00	213294	1.50	0.799		0.799
127.30	129.10	Py02 <b>Pyrite 02%</b> dark gray to greenish gray, mod-highly silicified, 3-5% diss. Py, 60cm smokey Qtz injection almost // to CA	126.00	127.50	213295	1.50	0.447		0.447
			127.50	129.00	213296	1.50	1.900		1.900
			129.00	130.50	213297	1.50	0.811		0.811
			130.50	132.00	213298	1.50	1.860		1.860

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
131.70	162.20	Py04 <b>Pyrite 04%</b> light gray to light purple, loc. mod-highly silicified, overall 1-5% with loc. concentrations associated to smokey Qtz injections, loc. Py stringers associated to Chl. alteration, 1-2% Qtz-Carb injections@50-60TCA, chl. and/or silica filled microfractures  mineralization decreases to Tr-1% between 162.2-165m	132.00	133.50	213299	1.50	1.555		1.555
			133.50	135.00	213301	1.50	3.200	2.96	2.960
			135.00	136.50	213302	1.50	3.250	3.10	3.100
			136.50	138.00	213303	1.50	1.610		1.610
			138.00	139.50	213304	1.50	0.581		0.581
			139.50	141.00	213305	1.50	1.605		1.605
			141.00	142.50	213306	1.50	4.570	4.45	4.450
			142.50	144.00	213307	1.50	2.090		2.090
			144.00	145.50	213308	1.50	0.646		0.646
			145.50	147.00	213309	1.50	3.710	3.54	3.540
			147.00	148.50	213311	1.50	1.650		1.650
			148.50	150.00	213312	1.50	2.710		2.710
			150.00	151.50	213313	1.50	2.860		2.860
			151.50	153.00	213314	1.50	2.980		2.980
			153.00	154.50	213315	1.50	3.010	2.71	2.710
154.50	156.00	213316	1.50	2.320		2.320			
156.00	165.00	Chl; Ser; Pot <b>Chloritisation; Sericitisation; Potassic alteration</b> +/-+ chl&sericitized, loc. light pervasive K-alteration	156.00	157.50	213317	1.50	1.070		1.070
			157.50	159.00	213318	1.50	2.040		2.040
			159.00	160.50	213319	1.50	2.450		2.450
			160.50	162.00	213321	1.50	2.080		2.080
			162.00	163.50	213322	1.50	0.670		0.670
			163.50	165.00	213323	1.50	2.400		2.400
165.00	173.00	Sil; Chl <b>Silicification; Chloritisation</b> light-dark gray, mod-highly silicified, loc. hydrobrecciated with Qtz-Carb matrix, chl. filled microfractures along loc. foliation@35TCA, ~1% smokey Qtz, 1-2% (less than cm) Qtz-carb veinlets@40TCA							
165.00	173.00	Py02 <b>Pyrite 02%</b> light-dark gray, highly silicified, 1-3% of diss. Py loc. in stringers associated to chl. alteration, loc. brecciated with Qtz-Carb and/or Chl. matrix)	165.00	166.50	213324	1.50	2.920		2.920
165.10	165.30	VEI;25;Qz;T;50°; <b>Vein 25 Quartz Tension 50°</b>	166.50	168.00	213325	1.50	2.640		2.640
			168.00	169.50	213326	1.50	2.430		2.430

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		smokey Qtz vein	169.50	171.00	213327	1.50	3.180	3.17	3.170
			171.00	172.50	213328	1.50	3.470	3.26	3.260
			172.50	174.00	213329	1.50	2.170		2.170
173.00	189.00	Chl; Ser; Pot	174.00	175.50	213331	1.50	0.859		0.859
		<b>Chloritisation; Sericitisation; Potassic alteration</b>	175.50	177.00	213332	1.50	0.789		0.789
		+ / ++ chl&sericitized, loc. light pervasive K-alteration	177.00	178.50	213333	1.50	0.599		0.599
			178.50	180.00	213334	1.50	0.948		0.948
			180.00	181.50	213335	1.50	0.532		0.532
			181.50	183.00	213336	1.50	0.997		0.997
			183.00	184.50	213337	1.50	0.101		0.101
			184.50	186.00	213338	1.50	0.159		0.159
			186.00	187.50	213339	1.50	0.447		0.447
			187.50	189.00	213341	1.50	0.323		0.323
189.00		Fin du sondage							
		Nombre d'échantillons : 102							
		Nombre d'échantillons QAQC : 10							
		Longueur totale échantillonnée : 152.90							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
49.50	51.00	213240	O53Pb	1.50	0.654	0.654
78.00	79.50	213260	O15Pa	1.50	1.000	1.000
91.50	93.00	213270	m	1.50	<0.005	0.001
105.00	106.50	213280	O6Pc	1.50	1.535	1.535
118.50	120.00	213290	m	1.50	0.005	0.005
132.00	133.50	213300	O6Pc	1.50	1.615	1.615
145.50	147.00	213310	m	1.50	0.008	0.008
159.00	160.50	213320	O6Pc	1.50	1.590	1.590
172.50	174.00	213330	m	1.50	0.008	0.008
186.00	187.50	213340	O15Pa	1.50	1.015	1.015

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-84

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine

Foré par : Multidrill

Lot :

Décrit par : Aidamir Cheroukh

Du : 2009-11-01

Date de description : 2009-11-02

Au : 2009-11-02

Collet

UTM

Azimut : 156.17°

Plongée : -50.40°

Longueur : 180.00 m

Est 629 991.1

Nord 5 374 283.4

Élévation 282.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.34°	-50.76°	Non
Reflex	5.00	0.86°	-50.62°	Non
Reflex	8.00	1.28°	-50.25°	Non
Reflex	11.00	1.53°	-50.44°	Non
Reflex	14.00	1.58°	-50.74°	Non
Reflex	17.00	1.74°	-50.23°	Non
Reflex	20.00	1.83°	-49.96°	Non
Reflex	23.00	1.75°	-50.09°	Non
Reflex	26.00	1.92°	-50.32°	Non
Reflex	29.00	1.97°	-50.01°	Non
Reflex	32.00	1.87°	-49.62°	Non
Reflex	35.00	1.97°	-49.52°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.04°	-49.85°	Non
Reflex	41.00	2.22°	-49.63°	Non
Reflex	44.00	2.25°	-49.18°	Non
Reflex	47.00	2.37°	-48.96°	Non
Reflex	50.00	2.47°	-49.18°	Non
Reflex	53.00	2.55°	-49.35°	Non
Reflex	56.00	2.66°	-49.23°	Non
Reflex	59.00	2.83°	-48.69°	Non
Reflex	62.00	2.94°	-48.53°	Non
Reflex	65.00	2.95°	-48.83°	Non
Reflex	68.00	2.86°	-48.90°	Non
Reflex	71.00	2.96°	-48.31°	Non

Description

GPS Datum NAD83, UTM Zone 17.

\*\*\*Qualified Person: F. T. Archibald (OGQ permit # 1159)

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	12.00	MT <b>Casing</b> Casing							
12.00	18.20	SY PT POR <b>Syenite Lath Porphyry Intrusive</b> greenish gray to dark gray, med. gnd matrix with 1-6% lath phenos(up to 0.5X3cm), partially K-altered and/or chl., mod-highly silicified with 1-3% diss. to dendritic Py loc. in mm-stringers, 1-2% Qtz-Carb. injections(less than cm)@50TCA gradual lower CT	12.00	13.50	220565	1.50	5.380	4.90	4.900
			13.50	15.00	220566	1.50	8.850	8.24	8.240
12.00	15.00	CNR <b>Core Not recovered</b> 40 cm of NRC							
12.00	18.00	Py02 <b>Pyrite 02%</b> lath syenite, silicified with 1-3% Py, disseminated, patchy or loc. in seams							
15.00	18.00	FRC <b>Fractured 70°</b> 1-5% fractured core	15.00	16.50	220567	1.50	2.640		2.640
			16.50	18.00	220568	1.50	1.155		1.155
			18.00	19.50	220569	1.50	1.735		1.735
18.20	84.10	SY POR <b>Syenite Porphyry Intrusive</b> greenish gray to light purple, 1-2% ghost lath phenos mainly chl., overall weak-mod. seric&chl. and loc. epidotized, loc.pervasive K-alteration, loc.hydrobrecciation with silica-carb matrix  overall Tr. of Py with 1-2%concentrations loc.  weak-mod. foliated@50TCA starting 39m, 1-3% less than cm silica-carb loc. irregular@40TCA  mod-high chl. starting 59.4m  gradual lower ct  **Local weak to moderate shearing typically sub-perpendicular TCA.	19.50	21.00	220571	1.50	0.012		0.012
			21.00	22.50	220572	1.50	0.064		0.064
			22.50	24.00	220573	1.50	0.099		0.099
			24.00	25.50	220574	1.50	0.006		0.006
			25.50	27.00	220575	1.50	0.054		0.054
			27.00	28.50	220576	1.50	0.084		0.084
			28.50	30.00	220577	1.50	0.199		0.199
			30.00	31.50	220578	1.50	0.975		0.975
			31.50	33.00	220579	1.50	1.910		1.910
32.30	33.00	I2D LT POR; LT <b>Syenite Lath Porphyry Intrusive; Lath</b> dark gray to greenish gray, 1-3% less than cm silica filled							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
32.30	33.00	microfractures loc@40TCA Py02 <b>Pyrite 02%</b> sams as 12-18m, +/- chl&+ seric.	33.00	34.50	220581	1.50	0.018		0.018
34.00	37.00	FRC <b>Fractured 85°</b> fractured core@-85TCA	34.50	36.00	220582	1.50	0.056		0.056
			36.00	37.50	220583	1.50	0.058		0.058
			37.50	39.00	220584	1.50	0.009		0.009
			39.00	40.50	220585	1.50	0.007		0.007
			40.50	42.00	220586	1.50	1.220		1.220
41.80	43.50	BRE <b>Breccia</b> silica-Carb matrix with angular mm-cm clasts, partially silicified, 1-2% finely diss. Py, chl. patches loc.	42.00	43.50	220587	1.50	1.870		1.870
			43.50	45.00	220588	1.50	0.005		0.005
			45.00	46.50	220589	1.50	0.010		0.010
			46.50	48.00	220591	1.50	<0.005		0.001
			48.00	49.50	220592	1.50	0.006		0.006
			49.50	51.00	220593	1.50	0.006		0.006
			51.00	52.50	220594	1.50	0.013		0.013
			52.50	54.00	220595	1.50	0.006		0.006
			54.00	55.50	220596	1.50	<0.005		0.001
			55.50	57.00	220597	1.50	0.006		0.006
			57.00	58.50	220598	1.50	0.005		0.005
41.80	42.30	Py01 <b>Pyrite 01%</b> 102% finely diss. Py	58.50	60.00	220599	1.50	0.005		0.005
59.40	64.05	Chl; Ser <b>Chloritisation; Sericitisation</b> greenish purple, ++ chl&+Ser., random chl. filled microfractures loc@40TCA							
59.70	64.00	CIS <b>Sheared</b> Weak to moderate shearing @ 90 DTCA. Moderate chlorite/sericite alteration. well foliated.	60.00	61.50	220601	1.50	0.043		0.043
			61.50	63.00	220602	1.50	0.084		0.084
			63.00	64.50	220603	1.50	0.082		0.082
			64.50	66.00	220604	1.50	<0.005		0.001
			66.00	67.50	220605	1.50	0.007		0.007
			67.50	69.00	220606	1.50	0.026		0.026
			69.00	70.50	220607	1.50	0.026		0.026

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
72.00	86.00	Chl; Ser <b>Chloritisation; Sericitisation</b> altered syenite, greenish gray, chl. filled microfractures, loc. brecciation, Tr. of Py	70.50	72.00	220608	1.50	0.009		0.009
			72.00	73.50	220609	1.50	0.040		0.040
			73.50	75.00	220611	1.50	0.029		0.029
			75.00	76.50	220612	1.50	0.021		0.021
			76.50	78.00	220613	1.50	0.132		0.132
			78.00	79.50	220614	1.50	0.107		0.107
			79.50	81.00	220615	1.50	0.055		0.055
			81.00	82.50	220616	1.50	0.048		0.048
			82.50	84.00	220617	1.50	0.237		0.237
			84.00	85.50	220618	1.50	0.784		0.784
84.10	120.90	BA; FOL; RUB <b>Mafic Meta-Volcanic ; Foliation ; Banded</b> light-dark green to loc. yellowish green mafic unit, rock is loc. massive, fine-med grained, loc. mod-strongly foliated@50TCA, 1-3% Qtz-Carb. injections(to hydrobrecciation loc.)@50TCA1-2% broken core, loc. bleached passages overall Tr. of Py, loc. cubic to cm sized stringers allong foliation  130.5-Xm: highly altered, friable V3 to shistic loc., highly chloritized& sericitized, banded, high carbonate alteration, loc. microfolded  **Local zones of interbedded argillite - example 87.4-90.0m.	85.50	87.00	220619	1.50	0.525		0.525
			87.00	88.50	220621	1.50	0.032		0.032
			88.50	90.00	220622	1.50	0.009		0.009
			90.00	91.50	D911459	1.50	0.137		0.137
			91.50	93.00	D911461	1.50	0.020		0.020
			93.00	94.50	D911462	1.50	0.016		0.016
			94.50	96.00	D911463	1.50	0.038		0.038
94.60	96.25	Ser; Chl <b>Sericitisation; Chloritisation</b> ++ chl.&seric, loc. hydrobracciation with silica-carb matrix	96.00	97.50	D911464	1.50	0.537		0.537
			97.50	99.00	D911465	1.50	0.030		0.030
			99.00	100.50	D911466	1.50	0.191		0.191
			100.50	102.00	D911467	1.50	0.112		0.112
			102.00	103.50	D911468	1.50	0.196		0.196
			103.50	105.00	D911469	1.50	0.067		0.067
			105.00	106.50	D911471	1.50	<0.005		0.001
			106.50	108.00	D911472	1.50	<0.005		0.001
108.00	111.00	Ser; Chl <b>Sericitisation; Chloritisation</b> mod-strong chl& seric, banded, loc. cm-sericite bands allong foliation							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
108.00	114.00	BC <b>Broken core</b> 1-3% broken core	108.00	109.50	D911473	1.50	0.006		0.006
			109.50	111.00	D911474	1.50	0.182		0.182
			111.00	112.50	D911475	1.50	0.243		0.243
			112.50	114.00	D911476	1.50	0.190		0.190
			114.00	115.50	D911477	1.50	0.006		0.006
			115.50	117.00	D911478	1.50	0.012		0.012
			117.00	118.50	D911479	1.50	0.010		0.010
			118.50	120.00	D911481	1.50	0.006		0.006
			120.00	121.50	D911482	1.50	0.013		0.013
			120.90	150.10	UM; RUB; CIS; BC <b>Ultramafic Volcanic (incl. Flows); Banded; Sheared;</b> <b>Broken core</b> light-dark green to yellowish green loc., highly talc-carb altered and deformed rock, friable fine grnd ultra-mafic?, loc shistose, banded, loc. microfolded, strongly foliated-sheared@70TCA, loc. cm-sized sericite stringers, loc. gabbroic texture, overall Tr. of Py with loc. concentration of coarse patchy Py to cubic loc. fractured upper CT, gradual lower CT	121.50	123.00	D911483	1.50
123.00	124.50	D911484				1.50	<0.005		0.001
124.50	126.00	D911486				1.50	0.006		0.006
126.00	127.50	D911487				1.50	0.005		0.005
127.50	129.00	D911488				1.50	<0.005		0.001
129.00	130.50	D911489				1.50	0.012		0.012
130.50	132.00	D911491				1.50	0.007		0.007
132.00	133.50	D911492				1.50	0.007		0.007
133.50	135.00	D911504				1.50	<0.005		0.001
135.00	136.50	D911493				1.50	<0.005		0.001
136.50	138.00	D911494				1.50	<0.005		0.001
138.00	139.50	D911495				1.50	<0.005		0.001
139.50	141.00	D911496				1.50	0.005		0.005
141.00	142.50	D911497				1.50	<0.005		0.001
142.50	144.00	D911498				1.50	0.006		0.006
144.00	145.50	D911499				1.50	<0.005		0.001
145.50	147.00	D911501				1.50	0.006		0.006
147.00	148.50	D911502				1.50	<0.005		0.001
148.50	150.00	D911503	1.50	0.005		0.005			
150.00	151.50	D911505	1.50	0.009		0.009			
120.90	150.00	Ta; Car <b>Talceous; Carbonatisation</b> strongly talc-carb. altered							
120.90	150.00	BRK; FRC; FTG; FAI <b>Broken ; Fractured; Gauge Fault; Fault</b>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
150.10	180.00	zone of deformation, strongly altered&highly deformed with 1-2% fault gauge and silica-carb fluids injections  strongly foliated to sheared@70TCA between 121.5-150  M8; FOL <b>Schiste; Foliation</b> light green to greenish gray, fine-med grained, mod-strongly foliated to loc. sheraed@70TCA, loc. shistose rock with 1-3% br> loc. microfolded, ** Also has a moderate to strong sedimentary component ( jasper lenses and other xenolithic fragments) EOH@180m	151.50	153.00	D911506	1.50	0.135		0.135
			153.00	154.50	D911507	1.50	0.014		0.014
			154.50	156.00	D911508	1.50	0.031		0.031
			156.00	157.50	D911509	1.50	0.028		0.028
			157.50	159.00	D911511	1.50	0.136		0.136
			159.00	160.50	D911512	1.50	0.088		0.088
			160.50	162.00	D911513	1.50	0.044		0.044
			162.00	163.50	D911514	1.50	0.044		0.044
			163.50	165.00	D911515	1.50	0.063		0.063
			165.00	166.50	D911516	1.50	0.026		0.026
166.00	180.00	FRC <b>Fractured 70°</b> fractured "chips"@70TCA	166.50	168.00	D911517	1.50	0.016		0.016
			168.00	169.50	D911518	1.50	0.007		0.007
			169.50	171.00	D911519	1.50	0.012		0.012
			171.00	172.50	D911521	1.50	0.005		0.005
			172.50	174.00	D911522	1.50	0.113		0.113
			174.00	175.50	D911523	1.50	0.091		0.091
			175.50	177.00	D911524	1.50	0.043		0.043
			177.00	178.50	D911525	1.50	0.014		0.014
			178.50	180.00	D911526	1.50	0.047		0.047
180.00		Fin du sondage Nombre d'échantillons : 112 Nombre d'échantillons QAQC : 14 Longueur totale échantillonnée : 168.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
18.00	18.00	220570	m	0.00	0.007	0.007
33.00	33.00	220580	O15Pa	0.00	1.010	1.010
45.00	45.00	220590	m	0.00	<0.005	0.001
58.50	58.50	220600	O15Pa	0.00	1.015	1.015
72.00	72.00	220610	m	0.00	<0.005	0.001
85.50	85.50	220620	O53Pb	0.00	0.650	0.650
90.00	91.50	D911460	D911459	1.50	0.108	0.108
103.50	103.50	D911470	O52Pb	0.00	0.320	0.320
117.00	118.50	D911480	D911479	1.50	0.008	0.008
123.00	123.00	D911485	m	0.00	<0.005	0.001
129.00	129.00	D911490	O53Pb	0.00	0.599	0.599
144.00	145.50	D911500	D911499	1.50	0.006	0.006
156.00	156.00	D911510	O54Pa	0.00	3.000	3.000
169.50	171.00	D911520	D911519	1.50	0.006	0.006

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-85	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau :
	Rang :	Place de travail : Beattie Mine
Foré par : Multidrill	Lot :	
Décrit par : A.Cheroukh	Du : 2009-11-01	Date de description : 2009-11-04
	Au : 2009-11-03	

Collet

Azimut : 345.50°  
 Plongée : -46.80°  
 Longueur : 171.00 m

UTM

Est	630 813.2
Nord	5 374 328.4
Élévation	310.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	6.00	359.63°	-44.28°	Non
Reflex	9.00	359.35°	-44.14°	Non
Reflex	12.00	359.36°	-44.09°	Non
Reflex	15.00	359.45°	-44.01°	Non
Reflex	18.00	359.62°	-43.93°	Non
Reflex	21.00	359.57°	-43.90°	Non
Reflex	24.00	359.69°	-43.82°	Non
Reflex	27.00	359.76°	-43.75°	Non
Reflex	30.00	359.85°	-43.81°	Non
Reflex	33.00	0.01°	-43.72°	Non
Reflex	36.00	1.09°	-43.66°	Non
Reflex	39.00	1.66°	-43.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	42.00	1.68°	-43.52°	Non
Reflex	45.00	2.05°	-43.45°	Non
Reflex	48.00	2.28°	-43.35°	Non
Reflex	51.00	2.46°	-43.26°	Non
Reflex	54.00	2.65°	-43.14°	Non
Reflex	57.00	2.87°	-43.03°	Non
Reflex	60.00	3.02°	-42.90°	Non
Reflex	63.00	3.08°	-42.81°	Non
Reflex	66.00	3.03°	-42.69°	Non
Reflex	69.00	3.19°	-42.60°	Non
Reflex	72.00	3.32°	-42.48°	Non
Reflex	75.00	3.35°	-42.35°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	0.40	MT <b>Casing</b> Casing							
0.27	15.25	Py05 <b>Pyrite 05%</b> 5-10% finely disseminated Py to coarse cubic in silicified syenite porphyry							
0.40	171.00	SY POR; AMY; PT; BX; FOL <b>Syenite Porphyry Intrusive; Amygdalaire; Lath; Breccia;</b> <b>Foliation</b> light-dark gray to wine red to yellowish green loc., fine-med. gnd, 1-5% ghost amygdules mainly chl. 1-2% lath phenos(up to 1X1.5cm) mainly K-altered, loc. oxidized joints, loc. weak-mod foliated@40-50TCA  1-2% Qtz-Carb injections(.cm-cm sized)@60TCA loc. K-altered  loc. oxides filled microfractures with dissolution cavities loc.  silica-filled(minor Crab) microfractures to hydrobrecciated, loc., chlorite matrix loc.  loc. seric-chl patches with local epidotization  1-2% loc. disseminated to coarse light-dark gray to black specularite  0.4-15.25m dark gray to greenish gray, silicified with 5-10% diss to coarse cubic Py, loc. +/+ epidotized, loc. brecciation  15.25-28m: wine red to reddish brown to buff yellowish, med.gnd, 1-4% mm-cm amygdules to lath phenos  171m EOH	0.40	1.50	220623	1.10	0.867		0.867
			1.50	3.00	220624	1.50	1.280		1.280
			3.00	4.50	220625	1.50	1.285		1.285
			4.50	6.00	220626	1.50	0.032		0.032
0.40	15.25	I2D LT POR; MNZD <b>Syenite Lath Porphyry Intrusive; Mineralized</b> silicified syenite, 5-10% diss. to coarse Py							
6.00	9.00	FRC <b>Fractured 60°</b> 1-2% fractured core	6.00	7.50	220627	1.50	4.740	4.56	4.560
			7.50	9.00	220628	1.50	7.890	7.56	7.560
			9.00	10.50	220629	1.50	1.995		1.995
			10.50	12.00	220631	1.50	2.690		2.690

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			12.00	13.50	220632	1.50	2.660		2.660
			13.50	15.00	220633	1.50	3.330	3.11	3.110
			15.00	16.50	220634	1.50	0.016		0.016
16.35	17.85	FRC <b>Fractured</b> rock fractured ~along CA	16.50	18.00	220635	1.50	0.005		0.005
18.00	19.70	Epi <b>Epidotisation</b> loc. pervasive epidotization	18.00	19.50	220636	1.50	0.005		0.005
			19.50	21.00	220637	1.50	<0.005		0.001
			21.00	22.50	220638	1.50	<0.005		0.001
			22.50	24.00	220639	1.50	<0.005		0.001
			24.00	25.50	220641	1.50	0.022		0.022
24.20	24.50	BX <b>Breccia</b> angular cm-sized fragments, silica-carb matrix, chlo. patches loc., 1-2% diss. specular Hm	25.50	27.00	220642	1.50	0.040		0.040
25.60	25.90	I2D LT POR; LT <b>Syenite Lath Porphyry Intrusive; Lath</b> 5-10% mm-cm lath phenos loc. chl., silica and/or chl. filled microfractures to loc. brecciated, Tr-2% diss. Py							
27.00	28.00	Ser; Chl <b>Sericitisation; Chloritisation</b> +/++ seric. /p>	27.00	28.50	220643	1.50	0.146		0.146
28.00	33.30	I2D POR; LT; MNZD <b>Syenite Porphyry Intrusive; Lath; Mineralized</b> silicified syenite porphyry with mod-highly epidotization&chlo, 2-3% up to 1X2cm lath phenos loc. slightly chl., 1-5% finely diss. Py to coarse loc. 1-3% ,cm-2cm Qtz-Carb injections@30TCA +/++ alb, gradual CT's							
28.00	33.30	Epi; Chl <b>Epidotisation; Chloritisation</b> siliceous syenite, +/++ epidotized, minor ch.&sericite	28.50	30.00	220644	1.50	0.061		0.061
			30.00	31.50	220645	1.50	0.094		0.094
			31.50	33.00	220646	1.50	0.156		0.156
			33.00	34.50	220647	1.50	0.593		0.593
28.00	30.23	Py02 <b>Pyrite 02%</b> Tr-2% diss. to coarse Py in silicified syenite, +/++epidot.&chl							
33.30	38.05	Sil; Epi; Hem	34.50	36.00	220648	1.50	0.232		0.232



Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	<b>Silicification; Epidotisation; Hematisation</b>	36.00	37.50	220649	1.50	0.049		0.049
	greenish gray to yellowish green, silicified to cherty, +/-+++ epidotized with minoe Chl., ++ K-altered Qtz-Carb injections, loc. Hm alteration intervals(up to 20cm) with dissolution cavities, Tr. of Chalcopy.	37.50	39.00	220651	1.50	0.267		0.267
38.35	38.80	Ser; Chl	39.00	40.50	220652	1.50	0.012	0.012
	<b>Sericitisation; Chloritisation</b>	40.50	42.00	220653	1.50	0.010		0.010
	greenish beige to rusty brown, hematized fracture joints, +/-++ seric&chl. weakly-mod foliated@40TCA, cm-patchy Qtz-Carb injections	42.00	43.50	220654	1.50	0.016		0.016
42.30	44.55	FOL	43.50	45.00	220655	1.50	0.458	0.458
	<b>Foliation 40°</b> weak-mod foliated@40TCA altered syenite							
44.55	49.85	BX; BSF						
	<b>Breccia; Breccia Silicified zone</b> dak gray to greenish gray, angular-subrounded mm-cm clasts, siliceous matrix with 1-5% finely diss. Py, loc. +/-++ epidotization, loc. + chl, altered fractured upper CT@50TCA-50TCA, gradual lower CT							
44.55	49.85	Py03	45.00	46.50	220656	1.50	1.930	1.930
	<b>Pyrite 03%</b> 1-5% finely diss. Py in brecciated syenite	46.50	48.00	220657	1.50	1.655		1.655
		48.00	49.50	220658	1.50	4.500	4.26	4.260
		49.50	51.00	220659	1.50	0.614		0.614
		51.00	52.50	220661	1.50	0.238		0.238
51.90	52.40	BX	52.50	54.00	220662	1.50	0.020	0.020
	<b>Breccia</b> silica matrix, loc. microbrecciated with ,cm-3cm angular clasts, + seric&chl.	54.00	55.50	220663	1.50	0.115		0.115
		55.50	57.00	220664	1.50	0.182		0.182
		57.00	58.50	220665	1.50	0.016		0.016
		58.50	60.00	220666	1.50	<0.005		0.001
		60.00	61.50	220667	1.50	<0.005		0.001
		61.50	63.00	220668	1.50	<0.005		0.001
		63.00	64.50	220669	1.50	0.079		0.079
		64.50	66.00	220671	1.50	<0.005		0.001
		66.00	67.50	220672	1.50	<0.005		0.001
		67.50	69.00	220673	1.50	0.047		0.047
		69.00	70.50	220674	1.50	0.011		0.011

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
70.95	71.25	Hem <b>Hematisation</b> + / ++ hematized, fractured core	70.50	72.00	220675	1.50	0.018		0.018
			72.00	73.50	220676	1.50	<0.005		0.001
			73.50	75.00	220677	1.50	0.110		0.110
			75.00	76.50	220678	1.50	0.015		0.015
			76.50	78.00	220679	1.50	<0.005		0.001
			78.00	79.50	220681	1.50	0.007		0.007
78.50	80.00	BRK <b>Broken</b> 1-4% broken core	79.50	81.00	220682	1.50	<0.005		0.001
			81.00	82.50	220683	1.50	<0.005		0.001
			82.50	84.00	220684	1.50	0.016		0.016
83.80	84.20	BX <b>Breccia</b> chl. filled microfractures to brecciated with chl. matrix	84.00	85.50	220685	1.50	0.155		0.155
84.30	92.55	Sil; Epi; Chl; Ser; Hem <b>Silicification; Epidotisation; Chloritisation;</b> <b>Sericitisation; Hematisation</b> silicified to chery loc., + / ++ chl & seric. with minor epidotization, loc. weak-mod foliated @ 50TCA, loc. chl. filed microfractures to brecciated loc. Tr-3% diss-coarse cubic Py, loc. + / ++ alb & ++ K-altered Qtz-carb injections up to 35cm	85.50	87.00	220686	1.50	0.034		0.034
84.30	84.65	VEI; 35; QzCbAb; T; ; Py01; <b>Vein 35 Quartz Carbonate Albite Tension Pyrite 01%</b> broken rock with irregular to ~// to CA Qtz-Carb injection, + / ++ alb, ++ K-altered, Tr-2% Py with Chl. & seric. original rock fragments	87.00	88.50	220687	1.50	0.388		0.388
			88.50	90.00	220688	1.50	0.065		0.065
			90.00	91.50	220689	1.50	0.290		0.290
			91.50	93.00	220691	1.50	0.274		0.274
			93.00	94.50	220692	1.50	0.825		0.825
93.30	93.65	Py03; Cp <b>Pyrite 03%; Chalcopyrite</b> silica fluids injections with 1-3% finely diss. Py to ,cm Py stringers, tr-1% Cp	94.50	96.00	220693	1.50	0.156		0.156
			96.00	97.50	220694	1.50	0.459		0.459
97.50	98.65	Chl; Ser <b>Chloritisation; Sericisation</b> light-yellowish green, mod. foliated @ 60TCA, ++ chl & +seric., ,cm-3cm Qtz-Carb injections	97.50	99.00	220695	1.50	0.093		0.093
			99.00	100.50	220696	1.50	0.006		0.006
			100.50	102.00	220697	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			102.00	103.50	220698	1.50		0.011	
			103.50	105.00	220699	1.50		0.005	0.005
			105.00	106.50	220701	1.50		0.006	0.006
			106.50	108.00	220702	1.50		0.179	0.179
			108.00	109.50	220703	1.50		0.019	0.019
			109.50	111.00	220704	1.50		0.313	0.313
			111.00	112.50	220705	1.50		0.392	0.392
			112.50	114.00	220706	1.50		0.047	0.047
			114.00	115.50	220707	1.50		0.239	0.239
114.35	116.15	Chl; Ser <b>Chloritisation; Sericitisation</b> ++chl(.cm patches to filled microfractures loc), +seric. 1-2% fractured core@50TCA, loc. Qtz-Carb injections, Tr-1%coarse cubic Py							
115.50	116.50	FRC; BC <b>Fractured 50°; Broken core</b> fractured core@50TCA + broken core(-1-2%)	115.50	117.00	220708	1.50		0.030	0.030
			117.00	118.50	220709	1.50		0.011	0.011
117.90	120.50	Chl; Ser <b>Chloritisation; Sericitisation</b> light-yellowish green, +/+ chl.&+ sericitization in the syenite, /p>	118.50	120.00	220711	1.50		0.032	0.032
			120.00	121.50	220712	1.50		0.016	0.016
			121.50	123.00	220713	1.50		0.005	0.005
122.00	126.00	Chl; Ser; Blch <b>Chloritisation; Sericitisation; Bleaching</b> light green to light purple altered syenite, chl. patches, ++/+++ chl&+seric., weak-mod foliated@70TCA	123.00	124.50	220714	1.50		0.005	0.005
			124.50	126.00	220715	1.50		0.005	0.005
			126.00	127.50	220716	1.50		0.012	0.012
			127.50	129.00	220717	1.50		0.009	0.009
			129.00	130.50	220718	1.50		0.006	0.006
			130.50	132.00	220719	1.50		0.005	0.005
			132.00	133.50	220721	1.50		0.016	0.016
			133.50	135.00	220722	1.50		0.009	0.009
134.60	136.00	Chl; Ser; Blch <b>Chloritisation; Sericitisation; Bleaching</b> lime green to yellowish green altered syenite, ++/+++ chl&+seric., strongly foliated-sheared@60TCA, Tr-1 diss. Py white-smoeky irreg. Qtz-Carb injections elongated chl. patches, loc. microfolding, partially broken core, Tr-2% coarse cubic, cm Py							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
134.60	136.00	FOL <b>Foliation 60°</b> strongly foliated-shered@60TCA	135.00	136.50	220723	1.50	0.038		0.038
			136.50	138.00	220724	1.50	1.955		1.955
137.80	140.00	Chl; Ser; Blch <b>Chloritisation; Sericitisation; Bleaching</b> same as 134.6-136m	138.00	139.50	220725	1.50	0.024		0.024
			139.50	141.00	220726	1.50	0.009		0.009
			141.00	142.50	220727	1.50	0.005		0.005
			142.50	144.00	220728	1.50	0.005		0.005
143.00	144.15	Chl; Ser; Blch <b>Chloritisation; Sericitisation; Bleaching</b> same as 134.6-136m	144.00	145.50	220729	1.50	0.005		0.005
			145.50	147.00	220731	1.50	0.019		0.019
			147.00	148.50	220732	1.50	0.005		0.005
			148.50	150.00	220733	1.50	0.053		0.053
			150.00	151.50	220734	1.50	0.006		0.006
			151.50	153.00	220735	1.50	0.016		0.016
			153.00	154.50	220736	1.50	0.007		0.007
154.20	157.80	Chl; Ser <b>Chloritisation; Sericitisation</b> +*/+++ chl.&+seric., 5-7% mm-cm chl. patches elongated along foliation@60TCA, rusty altered fractures, loc. irreg Qtz-Carb injections	154.50	156.00	220737	1.50	0.021		0.021
155.00	155.15	VEI;15;QzCbCl;30°; <b>Vein 15 Quartz Carbonate Chlorite 30°</b> Qtz-Carb injections@30TCA in the altered syenite	156.00	157.50	220738	1.50	0.012		0.012
			157.50	159.00	220739	1.50	0.023		0.023
			159.00	160.50	220741	1.50	0.019		0.019
159.30	162.00	Chl; Ser; Blch <b>Chloritisation; Sericitisation; Bleaching</b> same as 154.2-157.8m	160.50	162.00	220742	1.50	0.060		0.060
			162.00	163.50	220743	1.50	0.211		0.211
			163.50	165.00	220744	1.50	0.007		0.007
			165.00	166.50	220745	1.50	0.050		0.050
			166.50	168.00	220746	1.50	0.009		0.009
			168.00	169.50	220747	1.50	<0.005		0.001
			169.50	171.00	220748	1.50	<0.005		0.001
171.00	<b>Fin du sondage</b> Nombre d'échantillons : 114 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 170.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.00	10.50	220630	m	1.50	0.009	0.009
22.50	24.00	220640	O6Pc	1.50	1.635	1.635
36.00	37.50	220650	m	1.50	<0.005	0.001
49.50	51.00	220660	O6Pc	1.50	1.615	1.615
63.00	64.50	220670	m	1.50	<0.005	0.001
76.50	78.00	220680	O15Pa	1.50	0.994	0.994
90.00	91.50	220690	m	1.50	0.005	0.005
103.50	105.00	220700	O15Pa	1.50	1.025	1.025
117.00	118.50	220710	m	1.50	0.005	0.005
130.50	132.00	220720	O15Pa	1.50	1.025	1.025
144.00	145.50	220730	m	1.50	<0.005	0.001
157.50	159.00	220740	O15Pa	1.50	1.035	1.035

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-86

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine

Foré par : Multidrill

Lot :

Décrit par : A.Cheroukh

Du : 2009-11-06

Date de description : 2009-11-07

Au : 2009-11-07

Collet

UTM

Azimut : 357.42°

Plongée : -42.10°

Longueur : 150.00 m

Est 630 838.3

Nord 5 374 328.4

Élévation 311.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	350.00°	-42.48°	Non
Reflex	4.00	350.32°	-42.29°	Non
Reflex	8.00	350.60°	-41.91°	Non
Reflex	12.00	350.65°	-41.82°	Non
Reflex	16.00	350.66°	-42.22°	Non
Reflex	20.00	350.76°	-42.07°	Non
Reflex	24.00	351.14°	-41.54°	Non
Reflex	28.00	351.23°	-41.48°	Non
Reflex	32.00	351.04°	-41.70°	Non
Reflex	36.00	351.22°	-41.29°	Non
Reflex	40.00	351.38°	-40.95°	Non
Reflex	44.00	351.32°	-41.01°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	48.00	351.27°	-41.18°	Non
Reflex	52.00	351.48°	-41.00°	Non
Reflex	56.00	351.80°	-40.49°	Non
Reflex	60.00	351.83°	-40.50°	Non
Reflex	64.00	351.91°	-40.65°	Non
Reflex	68.00	352.20°	-40.14°	Non
Reflex	72.00	352.32°	-39.85°	Non
Reflex	76.00	352.25°	-40.09°	Non
Reflex	80.00	352.41°	-39.76°	Non
Reflex	84.00	352.65°	-39.27°	Non
Reflex	88.00	352.62°	-39.31°	Non
Reflex	92.00	352.69°	-39.51°	Non

Description

GPS Datum NAD83, UTM Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.00	MT <b>Casing</b> Casing							
3.00	150.00	SY PT POR; PT; BR; BSF <b>Syenite Lath Porphyry Intrusive; Lath; Brecciated; Breccia Silicified zone</b> wine red to light purple to greenish gray(in the silicified zones), weathered rusty&broken near the surface(3-6.7m), overall 1-4% lath phenos(up to 1X3cm) (mainly chl.) with Tr-1% pop-corn Fd phenos and minor rando amygdules, fine-med grained groundmass, 1-4% Qtz and/or Qtz-Carb injectionsloc.@50TCA, loc. silica and/or chl. filled microfractures leading to loc. silica-hydrobrecciation loc. epidotized passages up to 15cm, loc., overall Tr-2% diss. to coarse Py with concentrations up to 5% in silicified -epidotized zones  29.15-32.4m: strongly chloritized lath phenos  63.9-68.7m: loc. smokey qtz filled microfractures to up to 3cm silicified mineralized passages with less lath phenos(1-2% loc)  lath phenos decrease starting 75 to 1% to amygdulaire loc(2-5%) after 84m, elongated Chl. patche sallong foliation@70TCA  98.3-117m: different generations of Qtz-Carb injections(3-5%, br> less chloritization and stronger K-alteration starting 144M  EOH@150m	3.00	4.50	220749	1.50	0.104		0.104
			4.50	6.00	220751	1.50	1.410		1.410
			6.00	7.50	220752	1.50	1.635		1.635
3.00	6.70	Chl; Hem; Wea <b>Chloritisation; Hematisation; Weathering (Incl. Saproilitic alter.)</b> near the surface, broken core loc. +/++ chl, Hm++, weathered ++, vuggy appearance							
3.00	6.70	BC <b>Broken core</b> broken core, near the surface							
6.70	10.95	BX; MNZD; BSF <b>Breccia; Mineralized; Breccia Silicified zone</b> graysih purple to light-dark, silicified-brecciated syenite to white silica matrix supported smokey qtz breccia, irreg. Qtz-carb injections, chl. filled microfractures, loc. + epid. tr-2% diss. Py							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
6.70	10.95	with loc. 3-5% concentrations Sil; Epi; Chl <b>Silicification; Epidotisation; Chloritisation</b> greenish purple to light-dark gray, highly silicified syenite, loc. brecciated, white-smokey Qtz irreg. injections, chl. filled microfractures, + epidotization							
6.70	10.95	Py05 <b>Pyrite 05%</b> silicified, brecciated lath syenite, overall Tr-2% diss. to coarse Py with local concentrations up to 5%	7.50	9.00	220753	1.50	1.895	3.13	1.895
			9.00	10.50	220754	1.50	3.160		3.130
			10.50	12.00	220755	1.50	0.406		0.406
10.95	17.30	FRC <b>Fractured</b> loc. fractured allong CA	12.00	13.50	220756	1.50	0.055		0.055
			13.50	15.00	220757	1.50	0.070		0.070
			15.00	16.50	220758	1.50	0.022		0.022
			16.50	18.00	220759	1.50	0.179		0.179
17.30	19.25	BX; BSF; MNZD <b>Breccia; Breccia Silicified zone; Mineralized</b> greenish gray to greenish purple, +/+ chl. lath phenos, + epid., overall Tr-1% diss. py with loc. concentrations up to 3%, Tr. of Cp							
17.30	19.25	Sil; Epi; Chl <b>Silicification; Epidotisation; Chloritisation</b> greenish gray to greenish purple, highly silicified, loc. brecciated, +/+ chl lath phenos, overall Tr-1% with loc. concentration up to 3% diss. to coarse Py, + seric., Qtz-Carb injections@50TCA to loc. silica matrix brecciation, Tr. of cp							
17.30	19.25	Py03; Cp01 <b>Pyrite 03%; Chalcopyrite 01%</b> overall Tr-1% diss. Py with local concentrations up to 3%, Tr. of Cp	18.00	19.50	220761	1.50	0.093		0.093
			19.50	21.00	220762	1.50	0.029		0.029
			21.00	22.50	220763	1.50	0.333		0.333
21.35	27.80	Epi; Chl; Sil <b>Epidotisation; Chloritisation; Silicification</b> same as 17.3-19.25m, loc. epi-chl. bands(up to 2cm)@50TCA	22.50	24.00	220764	1.50	0.301		0.301
			24.00	25.50	220765	1.50	2.810		2.810
			25.50	27.00	220766	1.50	0.574		0.574
			27.00	28.50	220767	1.50	0.097		0.097
27.80	29.15	Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> pervasive epidotozation-seric., chl. filled microfractures, rusty altered fractures	28.50	30.00	220768	1.50	0.186		0.186



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
29.15	32.40	Chl <b>Chloritisation</b> strongly altered lath phenos in the syenite	30.00	31.50	220769	1.50	0.132		0.132
			31.50	33.00	220771	1.50	0.344		0.344
32.40	46.50	BX; BSF; MNZD <b>Breccia; Breccia Silicified zone; Mineralized</b> greenish gray to light purple, mod-strongly chloritized lath phenos, loc. silica hydro-brecciation, up to 15cm epidotized passages, Tr-2% diss. Py up to loc. 5% diss. to coarse Py							
32.40	46.50	Sil; Epi; Chl <b>Silicification; Epidotisation; Chloritisation</b> greenish gray to light purple, mod-strongly chloritized lath phenos, loc. silica hydro-brecciation, up to 15cm epidotized passages, Tr-2% diss. Py up to loc. 5% diss. to coarse Py							
32.40	46.50	Py05 <b>Pyrite 05%</b> silicified, loc. brecciated lath syenite, overall Tr-2% diss. to coarse Py with local concentrations up to 3-5%	33.00	34.50	220772	1.50	0.763		0.763
			34.50	36.00	220773	1.50	2.050		2.050
			36.00	37.50	220774	1.50	1.045		1.045
			37.50	39.00	220775	1.50	0.553		0.553
			39.00	40.50	220776	1.50	0.594		0.594
			40.50	42.00	220777	1.50	0.722		0.722
			42.00	43.50	220778	1.50	0.689		0.689
			43.50	45.00	220779	1.50	0.553		0.553
			45.00	46.50	220781	1.50	2.780		2.780
			46.50	47.10	Chl; Ser <b>Chloritisation; Sericitisation</b> light green altered syenite, +/- chl, +seric	46.50	48.00		220782
48.00	49.50	220783				1.50	0.260	0.260	
49.10	52.70	TZ; BSF; BR; MNZD <b>Transitional Zone; Breccia Silicified zone; Brecciated; Mineralized</b> altered to loc. brecciated syenite with silicified-brecciated passages(up to 20cm) with Tr-3% diss. py	49.50	51.00	220784	1.50	0.414		0.414
			51.00	52.50	220785	1.50	0.316		0.316
			52.50	54.00	220786	1.50	0.562		0.562
52.70	63.90	BX; BSF; MNZD <b>Breccia 55*; Breccia Silicified zone; Mineralized</b> silicified syenite to silica-smokey Qtz breccia, greenish beige bleached passages Tr-5% diss. py to ~2%@ lower CT, loc. + epidotization	54.00	55.50	220787	1.50	1.640	4.44	1.640
			55.50	57.00	220788	1.50	0.780		0.780
			57.00	58.50	220789	1.50	0.763		0.763
			58.50	60.00	220791	1.50	3.500		4.440
			60.00	61.50	220792	1.50	2.840		2.840
			61.50	63.00	220793	1.50	1.960		1.960
			63.00	64.50	220794	1.50	0.719	0.719	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
52.70	63.00	Py05 <b>Pyrite 05%</b> Tr-5% finely diss. Py to ~2% downward lower CT							
63.90	68.70	I2D POR; BR <b>Syenite Porphyry Intrusive; Brecciated</b> brecciated syentite with silica matrix, , overall Tr-2% with local. silicified passages with 3-5% diss. Py	64.50	66.00	220795	1.50	0.600		0.600
			66.00	67.50	220796	1.50	0.531		0.531
			67.50	69.00	220797	1.50	0.679		0.679
68.70	70.90	BX; BSF; MNZD <b>Breccia 90*; Breccia Silicified zone; Mineralized</b> light gray to blackish, mineralized, brecciated, silicified syenite							
68.70	70.90	Py07 <b>Pyrite 07%</b> mineralized breccia with 5-7% finely diss Py	69.00	70.50	220798	1.50	2.100		2.100
			70.50	72.00	220799	1.50	0.558		0.558
70.90	75.00	Chl; Ser; Epi <b>Chloritisation; Sericitisation; Epidotisation</b> smokey Qtz to silicified syentie breccia, ++/+++ chl, + seric., + epid Qtz-Carb irreg. injections between 73-74m							
70.90	75.00	BC <b>Broken core</b> 1% broken core in the breccia	72.00	73.50	220801	1.50	0.132		0.132
			73.50	75.00	220802	1.50	0.123		0.123
75.00	78.00	Chl <b>Chloritisation</b> mm elongated patches allong foliation	75.00	76.50	220803	1.50	0.021		0.021
			76.50	78.00	220804	1.50	0.119		0.119
			78.00	79.50	220805	1.50	0.451		0.451
			79.50	81.00	220806	1.50	0.023		0.023
			81.00	82.50	220807	1.50	0.011		0.011
			82.50	84.00	220808	1.50	0.008		0.008
			84.00	85.50	220809	1.50	0.005		0.005
			85.50	87.00	220811	1.50	0.008		0.008
			87.00	88.50	220812	1.50	0.006		0.006
			88.50	90.00	220813	1.50	0.019		0.019
			90.00	91.50	220814	1.50	0.019		0.019
			91.50	93.00	220815	1.50	0.024		0.024
			93.00	94.50	220816	1.50	0.024		0.024
			94.50	96.00	220817	1.50	0.020		0.020
95.90	98.30	Chl; Ser <b>Chloritisation; Sericitisation</b>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
95.90	98.30	greenish gray to dark green altered syenite, mod-strong foliated@50TCA with cm Qtz-Carb@50TCA FOL Foliation 50° mod-strong, foliated@50TCA	96.00	97.50	220818	1.50	0.032		0.032
			97.50	99.00	220819	1.50	0.015		0.015
			99.00	100.50	220821	1.50	0.024		0.024
			100.50	102.00	220822	1.50	0.076		0.076
			102.00	103.50	220823	1.50	0.022		0.022
			103.50	105.00	220824	1.50	0.346		0.346
			105.00	106.50	220825	1.50	0.903		0.903
			106.50	108.00	220826	1.50	0.141		0.141
			108.00	109.50	220827	1.50	0.092		0.092
			109.50	111.00	220828	1.50	0.266		0.266
			111.00	112.50	220829	1.50	0.025		0.025
112.50	117.00	Chl; Ser; Blich Chloritisation; Sericitisation; Bleaching greenish beige to light-greenish purple altered syenite porphyry, +/- chl+seric., chl. filled microfractures. 1-2% broken core, partially bleached, Tr-1% coarse cubic Py	112.50	114.00	220831	1.50	0.104		0.104
			114.00	115.50	220832	1.50	0.005		0.005
			115.50	117.00	220833	1.50	0.012		0.012
			117.00	118.50	220834	1.50	0.011		0.011
			118.50	120.00	220835	1.50	0.011		0.011
			120.00	121.50	220836	1.50	0.023		0.023
			121.50	123.00	220837	1.50	0.112		0.112
			123.00	124.50	220838	1.50	0.010		0.010
			124.50	126.00	220839	1.50	0.013		0.013
			126.00	127.50	220841	1.50	0.028		0.028
			127.50	129.00	220842	1.50	0.035		0.035
129.00	130.50	220843	1.50	0.054		0.054			
130.30	131.50	Chl Chloritisation 5-10% /p>							
130.30	131.50	FOL Foliation 50° mod-strong, foliated@40-60TCA	130.50	132.00	220844	1.50	0.015		0.015
			132.00	133.50	220845	1.50	0.009		0.009
			133.50	135.00	220846	1.50	0.008		0.008
			135.00	136.50	220847	1.50	0.012		0.012
			136.50	138.00	220848	1.50	0.008		0.008
			138.00	139.50	220849	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
144.00	150.00	Pot; Chl <b>Potassic alteration; Chloritisation</b> pervasive K-alteration, slightly chl.	139.50	141.00	220851	1.50	0.005		0.005
			141.00	142.50	220852	1.50	0.014		0.014
			142.50	144.00	220853	1.50	0.011		0.011
			144.00	145.50	220854	1.50	0.012		0.012
			145.50	147.00	220855	1.50	0.023		0.023
			147.00	148.50	220856	1.50	0.016		0.016
			148.50	150.00	220857	1.50	0.008		0.008
			150.00			Fin du sondage Nombre d'échantillons : 98 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 147.00			

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
3.00	4.50	220750	m	1.50	0.006	0.006
16.50	18.00	220760	O6Pc	1.50	1.555	1.555
30.00	31.50	220770	m	1.50	<0.005	0.001
57.00	58.50	220790	m	1.50	0.009	0.009
70.50	72.00	220800	O6Pc	1.50	1.525	1.525
84.00	85.50	220810	m	1.50	<0.005	0.001
97.50	99.00	220820	O53Pb	1.50	0.623	0.623
111.00	112.50	220830	m	1.50	0.008	0.008
124.50	126.00	220840	O53Pb	1.50	0.649	0.649
138.00	139.50	220850	m	1.50	0.008	0.008

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-87

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine

Foré par : Multidrill

Lot :

Décrit par : A.Cheroukh

Du : 2009-11-08

Date de description : 2009-11-09

Au : 2009-11-09

Collet

UTM

Azimut : 345.55°

Plongée : -54.00°

Longueur : 227.00 m

Est 630 817.3

Nord 5 374 304.2

Élévation 306.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.61°	-54.61°	Non
Reflex	5.00	1.19°	-54.54°	Non
Reflex	8.00	1.18°	-54.61°	Non
Reflex	11.00	1.48°	-54.46°	Non
Reflex	14.00	0.55°	-53.69°	Non
Reflex	17.00	1.96°	-54.12°	Non
Reflex	20.00	2.00°	-54.05°	Non
Reflex	23.00	359.87°	-53.74°	Oui
Reflex	26.00	1.43°	-54.01°	Non
Reflex	29.00	1.79°	-53.86°	Non
Reflex	30.00	0.40°	-53.40°	Non
Reflex	32.00	1.97°	-53.75°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	35.00	0.06°	-53.27°	Non
Reflex	38.00	1.07°	-52.89°	Non
Reflex	41.00	1.40°	-53.53°	Non
Reflex	44.00	2.23°	-53.20°	Oui
Reflex	47.00	1.52°	-52.64°	Non
Reflex	50.00	0.43°	-52.86°	Non
Reflex	53.00	0.63°	-52.81°	Non
Reflex	56.00	2.39°	-52.80°	Oui
Reflex	59.00	0.94°	-52.51°	Non
Reflex	62.00	1.90°	-52.80°	Non
Reflex	65.00	1.53°	-52.73°	Non
Reflex	68.00	1.23°	-52.58°	Non

Description

UTM NAD 83 Zone 17.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.60	MT <b>Casing</b> Casing, 35cm recovered							
3.50	11.40	Chl; Epi; Ser; Blch <b>Chloritisation; Epidotisation; Sericitisation; Bleaching</b> + /+++ chl, +epid, +seric, + /+++ bleached syenite							
3.60	227.00	SY POR <b>Syenite Porphyry Intrusive</b> 3.5-24.6m: altered, discolored(bleached) syenitic intrusive varying from greenish beige, dark green to dark gray, med. grained with finer grained silicified passages, groundmass is overall subject of chl-seric-epid(loc) and alteration of variable intensities, loc. bleached passages with loc. chl. filled microfractures.  1-3% broken core  loc. silicified to smokey Qtz injected with 3-5% of stringers or diss. py(15cm-1m) gradual silicification and more chl. microfractures downward the lower CT with the breccia  24.6-42.6 silicified, brecciated, mineralized zone with 5-10% diss. Py  large (2X3.5cm) Chl. patches to bands(~3cm)@35TCA associated to +alb.Qtz-Carb injections, loc. K-alteration  weak-non magnetic  larger (15cm-1.5m)chloritized intervals in sub-sheared zones starting 188m  EOH@227m	3.60	5.00	220858	1.40	0.057		0.057
			5.00	6.50	220859	1.50	3.660	3.20	3.200
5.85	6.20	Py05 <b>Pyrite 05%</b> white-smokey Qtz injections with Tr-5% diss. Py	6.50	8.00	220861	1.50	0.088		0.088
			8.00	9.50	220862	1.50	0.056		0.056
			9.50	11.00	220863	1.50	5.980	6.13	6.130
			11.00	12.50	220864	1.50	0.069		0.069
11.40	13.00	Chl <b>Chloritisation</b> ++ /+++ chl. pervasive alteration, loc. chl. filled microfractures	12.50	14.00	220865	1.50	0.032		0.032

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
13.00	15.30	Chl; Blch <b>Chloritisation; Bleaching</b> + /++ chl., + bleached, chl. filled microfractures@20TCA	14.00	15.50	220866	1.50	0.013		0.013
15.30	16.50	Blch; Chl <b>Bleaching; Chloritisation</b> + bleached, + /++ chl.	15.50	17.00	220867	1.50	0.070		0.070
16.50	18.90	Py <b>Pyrite</b> 3-5% diss. Py in silicified, Qtz-Catrb. injected syenite	17.00	18.50	220868	1.50	4.540	4.57	4.570
			18.50	20.00	220869	1.50	0.019		0.019
18.90	23.00	Chl; Blch; Epi <b>Chloritisation; Bleaching; Epidotisation</b> yellowish green, + /++ chl., + /++ bleached, + epid., rusty altered fractures	20.00	21.50	220871	1.50	0.020		0.020
			21.50	23.00	220872	1.50	0.009		0.009
23.00	24.70	Sil; Chl; Epi <b>Silicification; Chloritisation; Epidotisation</b> + /++ silicified, + epid., chl. filled microfractures along foliation or @15TCA loc., 15cm of silicified, brecciated passage with Tr-2% diss. Py	23.00	24.50	220873	1.50	0.017		0.017
			24.50	26.00	220874	1.50	1.805		1.805
24.60	42.60	BX; BSF <b>Breccia; Breccia silicified zone</b> silicified, loc. brecciated syenite, loc. white silica supported matrix, loc. slightly chl&+epid., angular to sub-rounded mm-cm sized clasts, 3-6% of py(patchy, diss. or in stringers) 1-3% br> 2-4% Fd porphyrs loc. chloritized between 34-42.6m  loc. oxides filled microfractures, 1-3% broken core  loc. chl. filled microfractures, silicification decreases gradually downward lower CT  upper Ct@20TCA, lower CT@40TCA							
24.60	42.60	Py <b>Pyrite</b> Tr-5 to 10% loc. of diss. Py in silicified, brecciated zone, white	26.00	27.50	220875	1.50	2.600		2.600
			27.50	29.00	220876	1.50	3.340	3.34	3.340



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		silica matrix with mm-cm sized clasts, + chl&epid	29.00	30.50	220877	1.50	1.585		1.585
		Py is in diss. in patches or stringers, gradual, fractured lower	30.50	32.00	220878	1.50	0.720		0.720
		CT@50TCA	32.00	33.50	220879	1.50	0.843		0.843
			33.50	35.00	220881	1.50	0.620		0.620
			35.00	36.50	220882	1.50	1.785		1.785
			36.50	38.00	220883	1.50	1.785		1.785
38.00	39.50	BC	38.00	39.50	220884	1.50	4.210	4.15	4.150
		<b>Broken core</b>	39.50	41.00	220885	1.50	6.010	5.60	5.600
		1-2% broken core with rusty oxidation products	41.00	42.50	220886	1.50	5.120	4.67	4.670
			42.50	44.00	220887	1.50	0.030		0.030
42.60	43.30	Chl; Ser							
		<b>Chloritisation; Sericitisation</b>							
		light-yellowish green, br>~1% /p>							
43.80	45.85	BX; BR	44.00	45.50	220888	1.50	0.008		0.008
		<b>Breccia; Brecciated</b>	45.50	47.00	220889	1.50	0.051		0.051
		breccia with mm-cm subrounded syenite clasts,							
		++chl&+seric.2-3% /p>							
45.85	51.95	Chl; Ser; Alb	47.00	48.50	220891	1.50	0.040		0.040
		<b>Chloritisation; Sericitisation; Albition</b>	48.50	50.00	220892	1.50	0.006		0.006
		yellowish green to light purple, +/+ chl, +seric, silica filled	50.00	51.50	220893	1.50	0.307		0.307
		microfractures to hydro-brecciated, loc.+ epid.	51.50	53.00	220894	1.50	0.005		0.005
		chl. filled microfractures, loc. br>1% broken core	53.00	54.50	220895	1.50	0.005		0.005
			54.50	56.00	220896	1.50	0.006		0.006
			56.00	57.50	220897	1.50	0.026		0.026
			57.50	59.00	220898	1.50	<0.005		0.001
			59.00	60.50	220899	1.50	0.023		0.023
			60.50	62.00	220901	1.50	0.010		0.010
62.00	73.60	Chl; Ser; Sil	62.00	63.50	220902	1.50	0.016		0.016
		<b>Chloritisation; Sericitisation; Silicification</b>	63.50	65.00	220903	1.50	0.145		0.145
		light-yellowish green to light-dark green loc.	65.00	66.50	220904	1.50	0.038		0.038
		+/+++ chl, slightly seric., loc. silicified&brecciated 10-20cm	66.50	68.00	220905	1.50	0.008		0.008
		passages with Tr-1% diss. Py	68.00	69.50	220906	1.50	0.080		0.080
69.20	73.60	FOL	69.50	71.00	220907	1.50	0.044		0.044
		<b>Foliation 50°</b>	71.00	72.50	220908	1.50	0.014		0.014
		weak-mod. foliated@50TCA							

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
73.60	84.65	Chl; Ser <b>Chloritisation; Sericitisation</b> chl and/or silica filled microfractures leading to loc. brecciation, overall +/++ chl&+seric 1-2% broken core  weak-mod. foliated@50TCA	72.50	74.00	220909	1.50	0.018		0.018	
			74.00	75.50	220911	1.50	0.128		0.128	
			75.50	77.00	220912	1.50	0.009		0.009	
			77.00	78.50	220913	1.50	0.008		0.008	
			78.50	80.00	220914	1.50	0.025		0.025	
			80.00	81.50	220915	1.50	0.054		0.054	
			81.50	83.00	220916	1.50	0.306		0.306	
			83.00	84.50	220917	1.50	0.056		0.056	
			84.50	86.00	220918	1.50	0.041		0.041	
73.60	78.00	FOL <b>Foliation 50°</b> microfractured to brecciated loc. with chl and/or silica fillings, overakk +/++ chl&+seric weak-mod folaited@50TCA								
84.65	100.80	I2D LT POR; LT; FOL <b>Syenite Lath Porphyry Intrusive; Lath; Foliation</b> greenish purple to wine red to greenish gray, fine-med. gnd with 5-10% lath phenos(mm up to 0.5X1.5cm), loc. chloritized and/or K-altered loc. mod-strong. foliated@40-50TCA overall chl-seric-epi with variable intensities, chl. is patchy or fills microfractures random or allong foliation associated mostly to patchy seric alteration loc. silicified passages with Tr-5% diss. py(10-50cm) loc. pervasive K-eltartion irreg sharp upper CT	86.00	87.50	220919	1.50	0.145		0.145	
			87.50	89.00	220921	1.50	0.095		0.095	
			89.00	90.50	220922	1.50	0.121		0.121	
			90.50	92.00	220923	1.50	0.074		0.074	
84.65	87.50	Chl; Ser; Epi <b>Chloritisation; Sericitisation; Epidotisation</b> ++/+++ chl, +/++ seric, + epid. more chloritization downward the lower CT@65TA								
90.70	91.00	Chl; Ser <b>Chloritisation; Sericitisation</b> greenish beige to milky white(Qtz-carb injections), chl&seric. stringers	92.00	93.50	220924	1.50	0.061		0.061	
92.95	96.95	Pot; Chl; Ser <b>Potassic alteration; Chloritisation; Sericitisation</b> loc. pervasive K-alteration, +/++ chl, + seric	93.50	95.00	220925	1.50	0.041		0.041	
			95.00	96.50	220926	1.50	0.130		0.130	
			96.50	98.00	220927	1.50	0.783		0.783	

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
96.95	98.90	Sil; Chl <b>Silicification; Chloritisation</b> loc. silicified passages(96.95-98.15m, 98.45-98.9m) with 2-5% diss. Py, chl or silica matrix						
96.95	98.90	Py05 <b>Pyrite 05%</b> Tr-5% diss. Py in silicified lath syenitic intrusion	98.00	99.50	220928	1.50	0.190	0.190
			99.50	101.00	220929	1.50	0.070	0.070
100.80	106.80	Chl; Pot <b>Chloritisation; Potassic alteration</b> light green to greenish beige altered syenite, ++/+++ chl. (elongated patches to stringers@50TCA), ++ K-altered, 1-2% broken core						
100.80	106.80	BC <b>Broken core</b> 1-2% broken core	101.00	102.50	220931	1.50	0.023	0.023
			102.50	104.00	220932	1.50	0.146	0.146
			104.00	105.50	220933	1.50	0.133	0.133
			105.50	107.00	220934	1.50	0.237	0.237
			107.00	108.50	220935	1.50	0.007	0.007
			108.50	110.00	220936	1.50	0.007	0.007
			110.00	111.50	220937	1.50	0.007	0.007
			111.50	113.00	220938	1.50	0.007	0.007
			113.00	114.50	220939	1.50	0.010	0.010
			114.50	116.00	220941	1.50	0.006	0.006
			116.00	117.50	220942	1.50	0.007	0.007
			117.50	119.00	220943	1.50	0.007	0.007
			119.00	120.50	220944	1.50	0.007	0.007
			120.50	122.00	220945	1.50	0.184	0.184
121.60	121.90	Chl <b>Chloritisation</b> ++/+++ chl to shistose, broken core, Qtz-Carb irreg. injections	122.00	123.50	220946	1.50	0.008	0.008
			123.50	125.00	220947	1.50	0.006	0.006
124.80	134.20	Chl; Ser <b>Chloritisation; Sericitisation</b> light purple to light green, ++ chl&+seric., br> 1-3% oxidized broken core, loc. irreg.Qtz-Carb injections  more oxidation altered between 133.5-134.3m	125.00	126.50	220948	1.50	0.010	0.010
			126.50	128.00	220949	1.50	0.096	0.096
			128.00	129.50	220951	1.50	0.021	0.021
			129.50	131.00	220952	1.50	0.041	0.041
			131.00	132.50	220953	1.50	0.027	0.027
			132.50	134.00	220954	1.50	0.007	0.007
			134.00	135.50	220955	1.50	0.447	0.447

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
124.80	129.30	BC <b>Broken core</b> broken core							
135.05	136.70	Py03; Hm <b>Pyrite 03%; Hematite</b> light-greenish gray to light purple, loc. smokey Qtz filled microfractures with up to 2% diss. py, more microfractured to sub-brecciated @ end of the zone with Tr-3% br> +epidotization loc.  Tr-1% specularite	135.50	137.00	220956	1.50	1.015		1.015
			137.00	138.50	220957	1.50	0.015		0.015
			138.50	140.00	220958	1.50	0.030		0.030
138.85	140.00	Chl; Ser <b>Chloritisation; Sericitisation</b> light green to greenish purple, patchy chl.(mm-cm) elongated loc.@50TCA to cm random bands, loc. coarse cubic Py	140.00	141.50	220959	1.50	0.201		0.201
			141.50	143.00	220961	1.50	0.055		0.055
141.90	142.20	Chl; Ser <b>Chloritisation; Sericitisation</b> ++/+++ Chl., ++Seric., strobgly foliated@50TCA irreg. Qtz-Carb injections							
141.90	142.20	FOL <b>Foliation 50°</b> strongly foliated@50TCA altered syenite							
142.20	143.00	FOL <b>Foliation 60°</b> mod. foliated@60TCA	143.00	144.50	220962	1.50	0.010		0.010
			144.50	146.00	220963	1.50	<0.005		0.001
			146.00	147.50	220964	1.50	0.005		0.005
146.40	146.50	VEI;15;QzCb;;50°;; <b>Vein 15 Quartz Carbonate 50°</b> Chl+seric. altered, smokey Qtz-Carb irreg. injection, loc. K-alteration	147.50	149.00	220965	1.50	0.005		0.005
			149.00	150.50	220966	1.50	<0.005		0.001
			150.50	152.00	220967	1.50	<0.005		0.001
			152.00	153.50	220968	1.50	0.007		0.007
152.85	155.00	Chl; Ser <b>Chloritisation; Sericitisation</b> ++/+++ Chl, +/+++ Seric., mod-strongky foliated@50-60TCA, Qtz-Carb irreg injections, loc.@50TCA	153.50	155.00	220969	1.50	0.163		0.163
			155.00	156.50	220971	1.50	0.005		0.005
			156.50	158.00	220972	1.50	0.070		0.070
			158.00	159.50	220973	1.50	0.014		0.014
			159.50	161.00	220974	1.50	<0.005		0.001
			161.00	162.50	220975	1.50	<0.005		0.001
			162.50	164.00	220976	1.50	<0.005		0.001
			164.00	165.50	220977	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			165.50	167.00	220978	1.50		0.005		0.005
			167.00	168.50	220979	1.50		0.007		0.007
			168.50	170.00	220981	1.50		0.006		0.006
			170.00	171.50	220982	1.50		<0.005		0.001
			171.50	173.00	220983	1.50		0.011		0.011
			173.00	174.50	220984	1.50		0.033		0.033
			174.50	176.00	220985	1.50		0.016		0.016
			176.00	177.50	220986	1.50		0.009		0.009
			177.50	179.00	220987	1.50		0.006		0.006
			179.00	180.50	220988	1.50		0.020		0.020
			180.50	182.00	220989	1.50		0.075		0.075
			182.00	183.50	220991	1.50		<0.005		0.001
			183.50	185.00	220992	1.50		0.052		0.052
			185.00	186.50	220993	1.50		0.374		0.374
			186.50	188.00	220994	1.50		0.085		0.085
			188.00	189.50	220995	1.50		0.071		0.071
188.60	191.25	Chl; Ser; Car; Hem <b>Chloritisation; Sericitisation; Carbonatisation; Hematization</b> gradual Chl. & light sericitization starting with mm chl. patches elongated along foliation@40TCa to strongly chl, loc. hydro-brecciated with silica-carb matrix and chloritized clasts, loc. foliated to sheared, Qtz-carb altered rock, loc. hematization, coarse cubic Py								
188.60	191.25	FOL; BRE <b>Foliation 40°; Breccia</b> loc.mod-strong to sub-sheared. foliated@40TCA loc. hydrobrecciation with silica-carb matrix	189.50	191.00	220996	1.50		0.040		0.040
			191.00	192.50	220997	1.50		0.016		0.016
			192.50	194.00	220998	1.50		0.012		0.012
			194.00	195.50	220999	1.50		<0.005		0.001
			195.50	197.00	214001	1.50		<0.005		0.001
196.70	197.45	Chl; Ser; Car <b>Chloritisation; Sericitisation; Carbonatisation</b> same as 188.6-191.25m	197.00	198.50	214002	1.50		0.005		0.005
			198.50	200.00	214003	1.50		0.170		0.170
			200.00	201.50	214004	1.50		<0.005		0.001
			201.50	203.00	214005	1.50		<0.005		0.001
			203.00	204.50	214006	1.50		<0.005		0.001
			204.50	206.00	214007	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			206.00	207.50	214008	1.50	<0.005		0.001
			207.50	209.00	214009	1.50	<0.005		0.001
			209.00	210.50	214011	1.50	0.005		0.005
209.50	215.50	Chl; Ser; Car <b>Chloritisation; Sericitisation; Carbonatisation</b> gradual chl(with light sericitation), chl. filled microfractures loc. associated to silica filled microfractures to loc. sub-brecciated, going gradually to br>loc. microfolded	210.50	212.00	214012	1.50	15.500	15.50	15.500
			212.00	213.50	214013	1.50	0.110		0.110
212.70	215.50	FOL <b>Foliation 30°</b> strongly foliated-sheared altered syenite@30TCA, loc. microfolding	213.50	215.00	214014	1.50	0.118		0.118
			215.00	216.50	214015	1.50	0.007		0.007
			216.50	218.00	214016	1.50	0.014		0.014
217.10	219.05	Chl; Ser <b>Chloritisation; Sericitisation</b> ++/+++Chl, + seric, +alb. irreg. Qtz-Carb injections loc.@40TCA Chl forms varying from filled microfractures to /p>	218.00	219.50	214017	1.50	<0.005		0.001
			219.50	221.00	214018	1.50	<0.005		0.001
221.00	224.00	BC <b>Broken core</b> 3% broken core	221.00	222.50	214019	1.50	<0.005		0.001
			222.50	224.00	214021	1.50	0.005		0.005
223.60	227.00	Ser; Chl <b>Sericitisation; Chloritisation</b> +/-++ Chl&+/-++ Seric groundmass, loc. Chl. filled microfractures, loc. microfolded cm-sized +alb.Qtz-Carb veins Tr-2% coarse cubic Py	224.00	225.50	214022	1.50	0.060		0.060
			225.50	227.00	214023	1.50	0.135		0.135
227.00	Fin du sondage Nombre d'échantillons : 149 Nombre d'échantillons QAQC : 17 Longueur totale échantillonnée : 223.40								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.00	6.50	220860	O15Pa	1.50	1.030	1.030
18.50	20.00	220870	m	1.50	<0.005	0.001
32.00	33.50	220880	O6Pc	1.50	1.585	1.585
45.50	47.00	220890	m	1.50	<0.005	0.001
59.00	60.50	220900	O15Pa	1.50	1.015	1.015
72.50	74.00	220910	m	1.50	0.008	0.008
86.00	87.50	220920	O15Pa	1.50	1.050	1.050
99.50	101.00	220930	m	1.50	0.007	0.007
113.00	114.50	220940	O53Pb	1.50	0.629	0.629
126.50	128.00	220950	m	1.50	0.006	0.006
140.00	141.50	220960	O15Pa	1.50	0.985	0.985
153.50	155.00	220970	m	1.50	<0.005	0.001
167.00	168.50	220980	O15Pa	1.50	1.000	1.000
180.50	182.00	220990	m	1.50	<0.005	0.001
194.00	195.50	221000	O15Pa	1.50	1.005	1.005
207.50	209.00	214010	m	1.50	<0.005	0.001
221.00	222.50	214020	O53Pb	1.50	0.621	0.621

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-88

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine

Foré par : Multi Drill

Lot :

Décrit par : A.Cheroukh & H.Tazerout

Du : 2009-11-11

Date de description : 2009-11-12

Au : 2009-11-12

Collet

UTM

Azimut : 352.40°

Plongée : -54.40°

Longueur : 240.00 m

Est 630 839.6

Nord 5 374 305.3

Élévation 309.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	351.35°	-53.62°	Non
Reflex	6.00	351.22°	-53.62°	Non
Reflex	9.00	351.65°	-53.55°	Non
Reflex	12.00	352.39°	-53.47°	Non
Reflex	15.00	353.49°	-53.44°	Non
Reflex	18.00	354.32°	-53.33°	Non
Reflex	21.00	354.91°	-53.21°	Non
Reflex	24.00	355.49°	-53.15°	Non
Reflex	27.00	355.84°	-53.09°	Non
Reflex	30.00	356.31°	-53.16°	Non
Reflex	33.00	355.88°	-52.94°	Non
Reflex	36.00	356.27°	-52.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	356.52°	-52.83°	Non
Reflex	42.00	356.68°	-52.72°	Non
Reflex	45.00	356.90°	-52.57°	Non
Reflex	48.00	357.22°	-52.42°	Non
Reflex	51.00	357.14°	-52.25°	Non
Reflex	54.00	357.45°	-52.23°	Non
Reflex	57.00	356.47°	-51.91°	Non
Reflex	60.00	356.79°	-51.82°	Non
Reflex	63.00	356.93°	-51.69°	Non
Reflex	66.00	357.32°	-51.58°	Non
Reflex	69.00	357.11°	-51.47°	Non
Reflex	72.00	357.17°	-51.42°	Non

Description

UTM NAD 83 Zone 17

Single shots corrected for magnetic declinaison (-12.5 W)

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	240.00	<p>SY POR; PT; BR</p> <p><b>Syenite Porphyry Intrusive; Lath; Brecciated</b></p> <p>untill 4.5m :strongly altered, fractured, weathered syenite intrusive, colors vary from rusty brown to wine red to greenish gray, loc. 1-3% (0.5X1.5cm) lath phenos mainly chl.,groundmass is fine-med. gnd, overall +/++Chl&amp;+seric, loc. +epid.</p> <p>loc. rusty alteration around fractures, tecto-brecciated with chl. matrix to loc. hydro-brecciated with white silica matrix</p> <p>~1% br&gt;overall Tr-1% diss. Py with 1-5% py(diss. or patchy to dendritic loc.) in silicified, brecciated passages(7.85-8.45m, 2.6-4.8m) weak-mod. foliated@50TCA</p> <p>silicification and Chl. alteration grow up downward leading to completely silicified to smokey Qtz zone</p> <p>98.95m: brecciated, altered @upper Ct with the silicified, brecciated zone, wine red to light purple, 1-3% trace amygdules mainly chl. or K-altered, loc. hydrobrecciation with silica matrix, loc. someky Qtz filled microfractures with mm- py stringers</p> <p>loc. weak-mod. magnetic</p> <p>starting 216m: loc. up to ~10cm Qtz-Carb-Chl bands, slighttt alb., K-altered, loc. brecciated</p> <p>mod-strong chloritized porphyrs starting 177m</p> <p>speckled texture monzo gran textute with chl. flecks after 222m</p> <p>EOH@240m</p>	0.00	1.50	214026	1.50	0.078		0.078
			1.50	3.00	214027	1.50	0.057		0.057
2.60	4.80	<p>Py03</p> <p><b>Pyrite 03%</b></p> <p>Tr-3% diss. Py in silicified loc. brecc. syenite</p>	3.00	4.50	214028	1.50	1.070		1.070
			4.50	6.00	214029	1.50	0.313		0.313
			6.00	7.50	214031	1.50	<0.005		0.001
			7.50	9.00	P009538	1.50	0.550		0.550
7.85	8.45	<p>Py03</p> <p><b>Pyrite 03%</b></p> <p>Tr-3% diss. Py in silicified loc. brecc. syenite</p>	9.00	10.50	P009539	1.50	0.013		0.013
			10.50	12.00	P009540	1.50	0.304		0.304
11.35	34.95	<p>BX; BSF; Qz</p> <p><b>Breccia; Breccia silicified zone; Quartz</b></p> <p>light-dark gray to greenish gray to pale green, highly silicified to pure smokey Qtz passages, silica filled microfractures to loc.</p>							

Corporation Minière Osisko Div. Exploration

Description		Analyse							
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
11.35	34.95	brecciated(33.55-34.95m), loc.+epid and/or Chl(filling microfractures) Tr-7% diss. Py, loc. py is patchy or dendritic more brecciation and chl. starting 39.7m Py07 <b>Pyrite 07%</b> Tr-7% diss, dendritic, patchy Py in silicified zone	12.00	13.50	P009541	1.50	0.832	3.52	0.832
			13.50	15.00	P009542	1.50	1.015		1.015
			15.00	16.50	P009543	1.50	1.975		1.975
			16.50	18.00	P009544	1.50	0.477		0.477
			18.00	19.50	P009545	1.50	1.615		1.615
			19.50	21.00	P009547	1.50	0.898		0.898
			21.00	22.50	P009548	1.50	0.121		0.121
			22.50	24.00	P009549	1.50	0.941		0.941
			24.00	25.50	P009550	1.50	0.336		0.336
			25.50	27.00	P009551	1.50	3.760		3.520
			27.00	28.50	P009552	1.50	1.225		1.225
			28.50	30.00	P009553	1.50	0.607		0.607
			32.90	34.65	Epi; Chl <b>Epidotisation; Chloritisation</b> +/-+Chl, minor Epid?, silica filled microfractures in the silicified zone	33.00	34.50		214051
34.50	36.00	214052				1.50	0.018	0.018	
34.95	39.70	Blch; Chl <b>Bleaching; Chloritisation</b> highly bleached rock, slightly chl. loc., pale-yellowish green, fine gnd, weak-mod. foliated@45TCA, loc. chl. filled microfractures	36.00	37.50	214053	1.50	0.176	0.176	
			37.50	39.00	214054	1.50	0.007	0.007	
			39.00	40.50	214055	1.50	0.788	0.788	
39.70	98.95	BX; BSF; Qz <b>Breccia; Breccia silicified zone; Quartz</b> same as 11.35-34.95m, brecciation gets stronger after 48m with +/-+ epid. clasts, loc.smoeky Qtz filled microfractures associated to Py stringers  75.8-98.95m: banded appearance, larger bleached sterile pistachio green +/-+ Chl, +/-+ seric(minor epid?) passages(up to 120cm) and silicified-brecciated&mineralized passages are decreasing downward lower CT if the zone, loc. foliation@50TCA							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
39.70	98.95	br>							
		Py05	40.50	42.00	214056	1.50	0.390		0.390
		<b>Pyrite 05%</b>	42.00	43.50	214057	1.50	2.030		2.030
		Tr-5% diss, dendritic, patchy Py in silicified zone	43.50	45.00	214058	1.50	0.339		0.339
			45.00	46.50	214059	1.50	1.500		1.500
			46.50	48.00	214061	1.50	12.050	12.05	12.050
48.00	63.00	Epi; Chl	48.00	49.50	214062	1.50	5.490	5.64	5.640
		<b>Epidotisation; Chloritisation</b>	49.50	51.00	214063	1.50	5.090	4.99	4.990
		+ /++ Chl, +Seric. in the silicified zone	51.00	52.50	214064	1.50	2.720		2.720
			52.50	54.00	214065	1.50	2.250		2.250
			54.00	55.50	214066	1.50	0.600		0.600
			55.50	57.00	214067	1.50	0.105		0.105
			57.00	58.50	214068	1.50	0.146		0.146
			58.50	60.00	214069	1.50	0.194		0.194
			60.00	61.50	214071	1.50	0.306		0.306
			61.50	63.00	214072	1.50	0.512		0.512
			63.00	64.50	214073	1.50	0.536		0.536
			64.50	66.00	214074	1.50	1.385		1.385
			66.00	67.50	214075	1.50	1.835		1.835
			67.50	69.00	214076	1.50	1.025		1.025
	69.00	70.50	214077	1.50	0.811		0.811		
	70.50	72.00	214078	1.50	1.870		1.870		
	72.00	73.50	214079	1.50	2.600		2.600		
	73.50	75.00	214081	1.50	5.730	5.71	5.710		
	75.00	76.50	214082	1.50	2.270		2.270		
75.45	75.60	VEI;15;Qz;T;30°;Py01; <b>Vein 15 Quartz Tension 30° Pyrite01%</b> Qtz-Carb injection@30TCa with Tr-1% diss. py							
75.80	98.95	Chl; Ser; Epi; Blch	76.50	78.00	214083	1.50	0.804		0.804
		<b>Chloritisation; Sericitisation; Epidotisation; Bleaching</b>	78.00	79.50	214084	1.50	0.279		0.279
		large(up to 120cm) of bleached, + /++Chl, + /++ Seric, epi+ /++ passages	79.50	81.00	214085	1.50	0.645		0.645
			81.00	82.50	214086	1.50	0.579		0.579
81.75	87.00	FRC; BC	82.50	84.00	214087	1.50	0.679		0.679
		<b>Fractured 50°; Broken core</b>	84.00	85.50	214088	1.50	0.103		0.103

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
1-2% fractured@50TCA, 1% broken, oxidized core			85.50	87.00	214089	1.50	0.226		0.226
			87.00	88.50	214091	1.50	0.641		0.641
			88.50	90.00	214092	1.50	0.045		0.045
			90.00	91.50	214093	1.50	0.085		0.085
			91.50	93.00	214094	1.50	0.153		0.153
			93.00	94.50	214095	1.50	0.453		0.453
			94.50	96.00	214096	1.50	1.015		1.015
			96.00	97.50	214097	1.50	1.995		1.995
			97.50	99.00	214098	1.50	2.820		2.820
			99.00	100.50	214099	1.50	0.074		0.074
			100.50	102.00	214101	1.50	0.015		0.015
			102.00	103.50	214102	1.50	0.405		0.405
			103.50	105.00	214103	1.50	0.008		0.008
			105.00	106.50	214104	1.50	0.044		0.044
			106.50	108.00	214105	1.50	0.015		0.015
108.00	109.50	214106	1.50	0.025		0.025			
108.65	110.40	Chl; Ser <b>Chloritisation; Sericitisation</b> + + / + + + Chl., + + + seric. / p >							
108.65	110.40	FOL <b>Foliation 40°</b> mod-strong. foliated@40TCA	109.50	111.00	214107	1.50	0.153		0.153
			111.00	112.50	214108	1.50	0.032		0.032
111.60	111.75	Chl <b>Chloritisation</b> strobgly chloritized	112.50	114.00	214109	1.50	<0.005		0.001
			114.00	115.50	214111	1.50	<0.005		0.001
			115.50	117.00	214112	1.50	0.033		0.033
			117.00	118.50	214113	1.50	<0.005		0.001
			118.50	120.00	214114	1.50	0.005		0.005
			120.00	121.50	214115	1.50	0.006		0.006
			121.50	123.00	214116	1.50	<0.005		0.001
			123.00	124.50	214117	1.50	0.007		0.007
			124.50	126.00	214118	1.50	0.007		0.007
126.00	133.60	Chl <b>Chloritisation</b> cm sized Chl.patches loc. elongated allong foliation, loc. foliated@60TCA	126.00	127.50	214119	1.50	0.005		0.005
			127.50	129.00	214121	1.50	0.022		0.022
			129.00	130.50	214122	1.50	0.027		0.027

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			130.50	132.00	214123	1.50	0.006		0.006
			132.00	133.50	214124	1.50	0.052		0.052
			133.50	135.00	214125	1.50	0.892		0.892
133.60	138.25	Chl; Ser <b>Chloritisation; Sericitisation</b> + / ++ Chl., +seric. foliated@40TCA, +alb. /p>							
133.70	135.40	Py04 <b>Pyrite 04%</b> 2-4% of smokey Qtz filled microfractures(to sub-brecciated loc.) associated to Tr-3% diss. to dendritic Py in the syenite intrusion loc. + / ++ Chl							
135.00	138.00	BC <b>Broken core</b> 2-3% broken core	135.00	136.50	214126	1.50	0.704		0.704
			136.50	138.00	214127	1.50	0.047		0.047
			138.00	139.50	214128	1.50	0.373		0.373
138.25	142.60	Py03 <b>Pyrite 03%</b> loc. bands(5-10cm) of microfractured(smoeky Qtz filled) to sub-brecciated passages in + / ++ chl. syenite Tr-3% diss to dendritic Py	139.50	141.00	214129	1.50	0.437		0.437
			141.00	142.50	214131	1.50	0.283		0.283
			142.50	144.00	214132	1.50	0.205		0.205
			144.00	145.50	214133	1.50	0.080		0.080
145.35	145.55	BX <b>Breccia</b> smokey Qtz injected with hematite filled cavities, Tr-1% diss. py	145.50	147.00	214134	1.50	0.012		0.012
			147.00	148.50	214135	1.50	0.062		0.062
147.45	148.25	Chl; Ser <b>Chloritisation; Sericitisation</b> + / + / + Chl., + / + / + Seric., mod-strong. foliated@50TCA, loc. fractured@60TCA							
147.45	148.25	FOL; FRC <b>Foliation ; Fractured</b> loc. foliated@50TCA, loc. fractured@60TCA	148.50	150.00	214136	1.50	0.005		0.005
149.00	150.00	FRC <b>Fractured</b> fractured core almost allong foliation	150.00	151.50	214137	1.50	<0.005		0.001
			151.50	153.00	214138	1.50	0.337		0.337
			153.00	154.50	214139	1.50	0.191		0.191
			154.50	156.00	214141	1.50	0.010		0.010
			156.00	157.50	214142	1.50	0.008		0.008
			157.50	159.00	214143	1.50	0.033		0.033
			159.00	160.50	214144	1.50	0.017		0.017
			160.50	162.00	214145	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			162.00	163.50	214146	1.50	0.011		0.011
			163.50	165.00	214147	1.50	0.042		0.042
			165.00	166.50	214148	1.50	0.039		0.039
165.65	167.10	Chl; Ser <b>Chloritisation; Sericitisation</b> ++Chl&+ Seric, weak-mod. foliated@60TCA, 1-2% coarse cubic Py							
165.65	167.10	FOL <b>Foliation 60°</b> weak-mod. foliated@60TCA	166.50	168.00	214149	1.50	<0.005		0.001
			168.00	169.50	214151	1.50	0.006		0.006
			169.50	171.00	214152	1.50	0.007		0.007
			171.00	172.50	214153	1.50	<0.005		0.001
			172.50	174.00	214154	1.50	<0.005		0.001
173.40	176.05	Chl; Ser; Alb; Pot <b>Chloritisation; Sericitisation; Albitisation; Potassic alteration</b> chl. filled microfractures loc. patchy, ++/+++Chl, ++/++Seric, 1% lath with chloritized borders loc. irreg. +/++alb. + K-altered Qtz-Carb injections	174.00	175.50	214155	1.50	0.317		0.317
			175.50	177.00	214156	1.50	0.008		0.008
			177.00	178.50	214157	1.50	0.013		0.013
			178.50	180.00	214158	1.50	0.008		0.008
178.80	179.60	Chl; Ser <b>Chloritisation; Sericitisation</b> +/++ Chl&Seric., loc. microfolded Qtz-Carb injections, loc. foliation@60TCA, loc. hydrobrecciated	180.00	181.50	214159	1.50	0.018		0.018
			181.50	183.00	214161	1.50	0.009		0.009
182.30	191.50	Pot <b>Potassic alteration</b> pervasive K-alteration	183.00	184.50	214162	1.50	0.032		0.032
			184.50	186.00	214163	1.50	0.214		0.214
			186.00	187.50	214164	1.50	0.006		0.006
			187.50	189.00	214165	1.50	<0.005		0.001
			189.00	190.50	214166	1.50	<0.005		0.001
			190.50	192.00	214167	1.50	0.059		0.059
191.50	192.75	Chl; Ser <b>Chloritisation; Sericitisation</b> +/++ Chl.&Seric, loc. pistachio green flecks(epidote?), mod. foliated@65TCA	192.00	193.50	214168	1.50	0.139		0.139
192.40	192.70	BX <b>Breccia</b> hydro-brecciated with chloritized&seric. clasts in a strongly carbonaceous matrix	193.50	195.00	214169	1.50	<0.005		0.001
			195.00	196.50	214171	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
195.50	197.50	Chl; Ser <b>Chloritisation; Sericitisation</b> ++/+++Chl. loc.microfolding, loc. foliated@40TCA, loc. Tr-2% Py, loc. +alb. Qtz-Carb injections	196.50	198.00	214172	1.50	0.039		0.039
			198.00	199.50	214173	1.50	0.074		0.074
			199.50	201.00	214174	1.50	<0.005		0.001
			201.00	202.50	214175	1.50	<0.005		0.001
			202.50	204.00	214176	1.50	<0.005		0.001
			204.00	205.50	214177	1.50	<0.005		0.001
			205.50	207.00	214178	1.50	<0.005		0.001
			207.00	208.50	214179	1.50	0.015		0.015
209.50	210.70	Chl; Ser; Alb <b>Chloritisation; Sericitisation; Albitisation</b> ++ Seric&Chl syenite porphyry, irreg. Qtz-Carb injections associated to Chl-Seric bands(+ alb.)loc. microfolding	208.50	210.00	214181	1.50	<0.005		0.001
			210.00	211.50	214182	1.50	0.007		0.007
			211.50	213.00	214183	1.50	<0.005		0.001
209.50	210.00	Cp01 <b>Chalcopyrite 01%</b> Tr-1% Chalcopyrite(cm Qtz-Carb injections(~ parallel to CA)	213.00	214.50	214184	1.50	<0.005		0.001
213.80	214.50	Chl; Ser <b>Chloritisation; Sericitisation</b> +/+Chl., ++/+++ Seric							
213.80	214.50	FOL <b>Foliation 50°</b> mod-highly foliated@50TCA	214.50	216.00	214185	1.50	<0.005		0.001
			216.00	217.50	214186	1.50	0.005		0.005
216.90	217.50	Pot <b>Potassic alteration</b> ++/+++ K-alteration	217.50	219.00	214187	1.50	0.007		0.007
218.00	219.00	Py02 <b>Pyrite 02%</b> Tr-2% coarse sub-cubic to cubic. Py	219.00	220.50	214188	1.50	0.006		0.006
219.70	221.20	Ser; Chl <b>Sericitisation; Chloritisation</b> ++/+++Seric., +/++Chl., Qtz-Carb injections with alb. borders, loc. microfolding, loc. chl. filled microfractures, Tr-2% diss. to coarse Py	220.50	222.00	214189	1.50	0.006		0.006
			222.00	223.50	214191	1.50	<0.005		0.001
			223.50	225.00	214192	1.50	<0.005		0.001
			225.00	226.50	214193	1.50	<0.005		0.001
			226.50	228.00	214194	1.50	<0.005		0.001
			228.00	229.50	214195	1.50	0.005		0.005
			229.50	231.00	214196	1.50	0.046		0.046
			231.00	232.50	214197	1.50	0.032		0.032

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	232.50	234.00	214198	1.50	0.008		0.008
	234.00	235.50	214199	1.50	0.009		0.009
	235.50	237.00	214201	1.50	0.007		0.007
	237.00	238.50	214202	1.50	0.006		0.006
	238.50	240.00	214203	1.50	0.113		0.113
<p>240.00 Fin du sondage            Nombre d'échantillons : 160            Nombre d'échantillons QAQC : 18            Longueur totale échantillonnée : 240.00</p>							



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.50	6.00	214030	m	1.50	<0.005	0.001
18.00	19.50	P009546	O6Pc	1.50	2.910	2.910
31.50	33.00	214050	m	1.50	<0.005	0.001
45.00	46.50	214060	O6Pc	1.50	1.580	1.580
58.50	60.00	214070	m	1.50	0.006	0.006
72.00	73.50	214080	O6Pc	1.50	1.590	1.590
85.50	87.00	214090	m	1.50	0.005	0.005
99.00	100.50	214100	O15Pa	1.50	0.969	0.969
112.50	114.00	214110	m	1.50	<0.005	0.001
126.00	127.50	214120	O53Pb	1.50	0.634	0.634
139.50	141.00	214130	m	1.50	<0.005	0.001
153.00	154.50	214140	O53Pb	1.50	0.637	0.637
166.50	168.00	214150	m	1.50	<0.005	0.001
180.00	181.50	214160	O53Pb	1.50	0.639	0.639
193.50	195.00	214170	m	1.50	<0.005	0.001
207.00	208.50	214180	O53Pb	1.50	0.636	0.636
220.50	222.00	214190	m	1.50	<0.005	0.001
234.00	235.50	214200	O53Pb	1.50	0.644	0.644

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-89

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau :

Rang :

Place de travail : Beattie Mine Site

Foré par : Multi Drilling

Lot :

Décrit par : C.W. Archibald

Du : 2009-11-14

Date de description : 2009-11-23

Au : 2009-11-16

Collet

UTM

Azimut : 344.63°

Plongée : -46.00°

Longueur : 180.00 m

Est 630 863.7

Nord 5 374 324.5

Élévation 312.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Flexite	6.00	0.76°	-46.76°	Non
Flexite	9.00	359.59°	-46.72°	Non
Flexite	12.00	0.98°	-46.16°	Non
Flexite	15.00	359.54°	-46.15°	Non
Flexite	18.00	358.30°	-46.27°	Non
Flexite	21.00	359.03°	-46.51°	Non
Flexite	24.00	359.85°	-45.87°	Non
Flexite	27.00	358.39°	-46.05°	Non
Flexite	33.00	0.92°	-45.96°	Non
Flexite	36.00	1.06°	-45.62°	Non
Flexite	39.00	358.85°	-45.73°	Non
Flexite	42.00	359.00°	-45.65°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Flexite	45.00	358.48°	-45.90°	Non
Flexite	48.00	358.81°	-45.83°	Non
Flexite	51.00	1.84°	-45.33°	Non
Flexite	54.00	1.37°	-45.22°	Non
Flexite	57.00	359.08°	-45.42°	Non
Flexite	63.00	359.25°	-45.32°	Non
Flexite	66.00	359.30°	-45.25°	Non
Flexite	69.00	359.43°	-45.14°	Non
Flexite	72.00	359.77°	-45.06°	Non
Flexite	75.00	0.88°	-45.06°	Non
Flexite	78.00	2.59°	-44.72°	Non
Flexite	81.00	2.36°	-44.40°	Non

Description

NAD 83, UTM Zone 17

Azimut corrected for magnetic declination (12.5 degrees w)

Resampled by C. Gagnier, Sept 2010.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	0.20	OV <b>Overburden</b> casing							
0.20	180.00	I2D POR <b>Syenite Porphyry Intrusive</b> Med-Drk purple/red, brick red, lt-med grn/grey; v.f.g. often aphanitic groundmass, with ~5-15% sub rnded to sub angular euhedral fspar phenos, 0.3-1.5cm x 0.75-2.0cm, often partially chl/ep/seric alt; generally massive, with some weak local shr/fol. @~40-60deg tca, non magnetic. Common light-med grn/ylw grn seric alt/flooding or wispy cob web stringers; common med-drk green chl alt; local weak minor silicific; occasional minor rusty red K/hem alt; rare alb alt; rusty brown oxidation of core at or near open fractures. Common to locally abnt qtz, qtz-fspar, qtz-fspar-carb veins/veinlets/stringers 0.2-3.0cm thick, randomly oriented with some preference for orientation @~25-40deg tca, often deformed/irregular/discontinuous/stkwk; Occasional minor felsic brecc.	0.20	1.50	D528601	1.30	0.044		0.044
			1.50	3.00	D528602	1.50	0.119		0.119
			3.00	4.50	D528603	1.50	0.054		0.054
			4.50	6.00	D528604	1.50	0.332		0.332
			6.00	7.50	D528605	1.50	0.749		0.749
			7.50	9.00	D528606	1.50	0.443		0.443
			9.00	10.50	D528607	1.50	0.174		0.174
			10.50	12.00	D528608	1.50	0.156		0.156
			12.00	13.50	D528609	1.50	0.080		0.080
			13.50	15.00	D528610	1.50	0.075		0.075
			15.00	16.50	D528611	1.50	0.031		0.031
			16.50	18.00	D528612	1.50	0.192		0.192
			18.00	19.50	D528613	1.50	0.189		0.189
			19.50	21.00	D528614	1.50	0.100		0.100
			21.00	22.50	D528616	1.50	0.034		0.034
			22.50	24.00	D528618	1.50	0.015		0.015
			24.00	25.50	D528619	1.50	0.060		0.060
24.95	25.30	CIS <b>Sheared</b> Ductile shear ~35cm core length; increased grn seric alt, some minor K alt, core bron, oxid/rusty.	25.50	27.00	D528620	1.50	0.065		0.065
			27.00	28.50	D528621	1.50	0.013		0.013
			28.50	30.00	D528622	1.50	0.031		0.031
			30.00	31.20	D528623	1.20	0.028		0.028
			31.20	32.70	210582	1.50	0.069		0.069
			32.70	34.20	210583	1.50	0.025		0.025
			34.20	35.90	D528624	1.70	0.146		0.146
			35.90	37.50	D528625	1.60	0.105		0.105
			37.50	39.00	D528626	1.50	0.568		0.568
			39.00	40.50	D528627	1.50	0.138		0.138
			40.50	42.00	D528628	1.50	0.194		0.194
			42.00	43.50	D528629	1.50	0.473		0.473
			43.50	45.00	D528630	1.50	0.669		0.669

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
45.20	52.35	Sil30; Ser15 <b>Silicification 30; Sericitisation 15</b> Core weak-mod altered, with Silicif ~30%, seric alt/local flooding ~15%; drk grey/purple; v.f.g. often aphanitic with ~5-10% faint/relict, rnded fspar phenos 0.3-1.0cm dia.; pervasive weak tension brecc with angular host rock frag/qtz-fspar fill; sheared near contacts @~40-50deg tca. Weakly mineralized, with up to 0.5% v.f.g. dissem py.	45.00	46.50	210584	1.50	0.830		0.830
45.20	52.35	Py0.5 <b>Pyrite 0.5%</b> Weakly mineralized wk-mod silicif zone with ~0.5% v.f.g. dissem py.	46.50	48.00	210585	1.50	1.480		1.480
			48.00	49.50	210586	1.50	1.110		1.110
			49.50	51.00	210587	1.50	0.873		0.873
			51.00	52.50	210588	1.50	0.197		0.197
			52.50	54.00	D528631	1.50	0.067		0.067
			54.00	55.50	D528632	1.50	0.292		0.292
			55.50	57.00	D528633	1.50	0.368		0.368
			57.00	58.50	D528634	1.50	0.270		0.270
			58.50	60.00	D528636	1.50	0.056		0.056
60.00	61.00	210589	1.00	0.090		0.090			
60.30	72.65	Sil25; Ser20; Alb03 <b>Silicification 25; Sericitisation 20; Albitisation 03</b> Moderately altered Syenite Porph with ~25% Silicif, ~20% Seric alt/flooding, tr. alb alt; v.f.g often aphanitic with up to ~5% relict fspar phenos locally.							
60.30	72.65	CIS; BRE <b>Sheared 50°; Breccia</b> Well sheared/fol @~45-60deg tca; pervasive brecciation, with angular/sub angular host rock fragments to 3cm, wht qtz/fspar/carb frac fill.							
60.30	72.65	Py0.5 <b>Pyrite 0.5%</b> Weakly mineralized mod silicif shear zone, with ~0.5- v.f.g. dissem py, rare f.g. conc py bands oriented parallel to shear.	61.00	62.00	210591	1.00	0.097		0.097
			62.00	63.00	210592	1.00	0.560		0.560
			63.00	64.00	210593	1.00	1.055		1.055
			64.00	65.00	210594	1.00	1.260		1.260
			65.00	66.00	210595	1.00	4.120	4.12	4.120
			66.00	67.00	210596	1.00	1.765		1.765
			67.00	68.00	210597	1.00	4.460	4.59	4.590

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			68.00	69.00	210598	1.00	5.380	5.56	5.560
			69.00	70.00	210599	1.00	2.630		2.630
			70.00	71.00	210601	1.00	1.165		1.165
			71.00	72.00	210602	1.00	0.904		0.904
			72.00	73.00	210603	1.00	0.592		0.592
			73.00	74.00	210604	1.00	0.940		0.940
			74.00	75.00	210605	1.00	0.976		0.976
			75.00	76.15	210606	1.15	0.211		0.211
			76.15	77.15	210607	1.00	1.280		1.280
76.50	77.00	Sil <b>Silicification</b> Weakly silicified, core med grey, v.f.g., phenos rnded/relict; weakly mineralized with ~0.5% v.f.g. dissem py.	77.15	78.50	D528638	1.35	0.255		0.255
			78.50	80.05	D528639	1.55	0.370	0.370	
			80.05	81.05	210608	1.00	0.447	0.447	
			81.05	81.55	210609	0.50	1.750	1.750	
81.10	81.55	BRE <b>Breccia</b> Minor qtz-fspar breccia, with sub angular to sub-rnded host rock fragments to 2cm; very weakly silicif; weakly mineralized with ~0.5% v.f.g. dissem py.	81.55	82.55	210611	1.00	0.136	0.136	
			82.55	84.00	D528641	1.45	0.150	0.150	
			84.00	85.50	D528642	1.50	0.141	0.141	
			85.50	87.00	D528643	1.50	0.051	0.051	
			87.00	88.40	D528644	1.40	<0.005	0.001	
			88.40	89.90	D528645	1.50	<0.005	0.001	
			89.90	91.30	D528646	1.40	<0.005	0.001	
			91.30	92.70	D528647	1.40	<0.005	0.001	
			92.70	94.20	D528648	1.50	0.064	0.064	
			94.20	95.80	D528649	1.60	0.028	0.028	
			95.80	96.80	210612	1.00	0.078	0.078	
96.00	96.45	CIS <b>Sheared 65°</b> Ductile shear @-65deg tca, angle becoming shallower with depth to 45deg tca; green sericitization, minor bluish qtz int; tr wisp py bands along shr plane.	96.80	98.60	D528650	1.80	0.155	0.155	
			98.60	100.40	D528651	1.80	0.131	0.131	
			100.40	102.00	D528652	1.60	0.015	0.015	
			102.00	103.50	D528653	1.50	0.006	0.006	
			103.50	105.00	D528654	1.50	<0.005	0.001	
			105.00	106.40	D528656	1.40	0.020	0.020	
			106.40	107.80	D528658	1.40	0.063	0.063	
107.80	108.20	STW;60%;Qz;G;;Py0.2; <b>Stockwerk 60% Quartz Concretion Pyrite0.2</b> Network of deformed stkwk veining, ~60%; Mostly white barren	107.80	108.80	210613	1.00	0.199	0.199	
			108.80	110.50	D528659	1.70	0.032	0.032	

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
qtz, with minor pinkish fspar, tr. carb; odd rnded or cubic py bleb in surrounding gm chl alt syen.	110.50	112.20	D528660	1.70	0.008		0.008	
	112.20	114.00	D528661	1.80	0.087		0.087	
	114.00	115.50	D528662	1.50	0.015		0.015	
	115.50	117.00	D528663	1.50	0.550		0.550	
	117.00	118.50	D528664	1.50	0.030		0.030	
	118.50	120.00	D528665	1.50	0.078		0.078	
	120.00	121.50	D528666	1.50	0.016		0.016	
	121.50	123.00	D528667	1.50	0.139		0.139	
	123.00	124.50	D528668	1.50	<0.005		0.001	
	124.50	126.00	D528669	1.50	0.026		0.026	
	126.00	127.50	D528670	1.50	0.005		0.005	
	127.50	129.00	D528671	1.50	0.059		0.059	
	129.00	130.50	D528672	1.50	0.217		0.217	
	130.50	132.00	D528673	1.50	0.015		0.015	
	132.00	133.50	D528674	1.50	<0.005		0.001	
	133.50	135.00	D528676	1.50	<0.005		0.001	
	135.00	136.50	D528678	1.50	<0.005		0.001	
	136.50	138.00	D528679	1.50	<0.005		0.001	
	138.00	139.50	D528681	1.50	<0.005		0.001	
	139.50	141.00	D528682	1.50	<0.005		0.001	
141.00	142.50	D528683	1.50	<0.005		0.001		
142.50	144.00	D528684	1.50	<0.005		0.001		
144.00	145.50	D528685	1.50	0.061		0.061		
145.50	147.00	D528686	1.50	0.014		0.014		
146.00	149.35	Chl80; Ser05 <b>Chloritisation 80; Sericitisation 05</b> Highly altered shear/breccia zone, stong chl alt, minor seric bands/stringers oriented parallel to shear, common minor qtz veins/veinlets to 1.5cm thick gen. oriented parallel to shear, some deformed irregular.						
146.00	149.35	CIS; BRE <b>Sheared 30°; Breccia</b> Highly altered brecciated shear zone, well sheared @~25-35deg tca, with ~15-20% angular to sub angular chloritized fragments 0.2-0.5cm x 0.5-2.0cm, usually oriented lengthwise parallel to	147.00	148.50	D528687	1.50	0.185	0.185
			148.50	150.00	D528688	1.50	0.011	0.011
			150.00	151.50	D528689	1.50	<0.005	0.001
			151.50	153.00	D528690	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		shear.	153.00	154.50	D528691	1.50	<0.005		0.001
			154.50	156.00	D528692	1.50	0.012		0.012
			156.00	157.50	D528693	1.50	0.012		0.012
			157.50	159.00	D528694	1.50	<0.005		0.001
			159.00	160.50	D528696	1.50	0.015		0.015
			160.50	162.00	D528698	1.50	0.006		0.006
			162.00	163.50	D528699	1.50	<0.005		0.001
			163.50	165.00	D528700	1.50	0.148		0.148
			165.00	166.50	D528701	1.50	<0.005		0.001
165.50	166.35	Chl75; Ser10 <b>Chloritisation 75; Sericitisation 10</b> mod to highly altered shear, pervasive green chloritization, with common/abnt seric stringers/flecs oriented parallel to shear, minor qtz-fspar, qtz-fspar-carb int to 4cm thick oriented parallel to shear.							
165.50	166.35	CIS <b>Sheared 65°</b> Moderately altered shear zone, well sheared/fol. @~65deg tca, with some wavy/crenulated fol.	166.50	168.00	D528702	1.50	<0.005		0.001
			168.00	169.50	D528703	1.50	<0.005		0.001
			169.50	171.00	D528704	1.50	<0.005		0.001
			171.00	172.50	D528705	1.50	<0.005		0.001
			172.50	174.00	D528706	1.50	<0.005		0.001
			174.00	175.50	D528707	1.50	<0.005		0.001
			175.50	177.00	D528708	1.50	<0.005		0.001
			177.00	178.50	D528709	1.50	<0.005		0.001
177.60	178.55	Chl50; Ser05 <b>Chloritisation 50; Sericitisation 05</b> Moderately chl altered syenite, med-drk grn, somewhat sheared @~65-70deg tca, with minor chloritized shardst to 0.3cm x 1cm. With large qtz-fspar-carb vein/dike 25cm core length.							
178.15	178.40	VEI;16;QzFpCb;G;60°; <b>Vein 16 Quartz Feldspath (alkaline) Carbonate Concretion 60°</b> Large Qtz-fspar-carb vein 25cm core length, 16cm thick, oriented ~60deg tca, sharp contacts, barren.	178.50	180.00	D528710	1.50	0.010		0.010

## Corporation Minière Osisko Div. Exploration

180.00

Fin du sondage

Nombre d'échantillons : 127

Nombre d'échantillons QAQC : 15

Longueur totale échantillonnée : 179.80



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
21.00	22.50	D528617	D528616	1.50	0.040	0.040
21.00	21.00	D528615	O54Pa	0.00	2.920	2.920
58.50	60.00	D528637	D528636	1.50	0.051	0.051
58.50	58.50	D528635	O61d	0.00	5.330	5.330
61.00	62.00	210590	m	1.00	<0.005	0.001
70.00	71.00	210600	O50Pb	1.00	0.859	0.859
80.05	80.05	D528640	m	0.00	<0.005	0.001
81.55	82.55	210610	m	1.00	0.005	0.005
105.00	105.00	D528655	O50Pb	0.00	0.880	0.880
106.40	106.40	D528657	D528656	0.00	0.013	0.013
133.50	133.50	D528677	D528676	0.00	<0.005	0.001
133.50	133.50	D528675	O52Pb	0.00	0.311	0.311
138.00	138.00	D528680	m	0.00	<0.005	0.001
159.00	160.50	D528697	D528696	1.50	0.011	0.011
159.00	159.00	D528695	O53Pb	0.00	0.631	0.631

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-90

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : Carl Corriveau

Du : 2009-11-10

Date de description : 2009-11-23

Au : 2009-11-13

Collet

UTM

Azimut : 165.30°

Plongée : -44.50°

Longueur : 234.00 m

Est 630 881.2

Nord 5 374 421.2

Élévation 311.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	15.00	170.00°	-45.00°	Non
Reflex	18.00	168.50°	-43.90°	Non
Reflex	21.00	168.90°	-43.80°	Non
Reflex	24.00	168.90°	-43.80°	Non
Reflex	27.00	169.60°	-43.70°	Non
Reflex	30.00	168.20°	-43.80°	Non
Reflex	33.00	168.80°	-43.80°	Non
Reflex	36.00	171.00°	-43.70°	Oui
Reflex	39.00	168.60°	-43.70°	Non
Reflex	42.00	169.90°	-43.70°	Non
Reflex	45.00	168.80°	-43.60°	Non
Reflex	48.00	169.00°	-43.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	51.00	169.70°	-43.60°	Non
Reflex	54.00	168.90°	-43.70°	Non
Reflex	57.00	170.90°	-43.50°	Non
Reflex	60.00	169.10°	-43.40°	Non
Reflex	63.00	170.50°	-43.40°	Non
Reflex	66.00	169.10°	-43.40°	Non
Reflex	69.00	169.90°	-43.40°	Non
Reflex	72.00	170.60°	-43.40°	Non
Reflex	75.00	169.70°	-43.30°	Non
Reflex	78.00	169.30°	-43.40°	Non
Reflex	81.00	169.40°	-43.40°	Non
Reflex	84.00	170.70°	-43.30°	Non

Description

GPS Datum NAD83, UTM Zone 17.

From 124.5m to 126m lost about 30cm of core, very fractured

Reflex azimuth values corrected for mag declinaison -12.5W

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	4.90	MT; MT <b>Overburden; Casing</b>							
4.90	5.60	SY; POR <b>Syenite; Porphyric</b> Redish to purple porphyritic syenite recuperate from casing (HQ). All core sent to lab for analysis. Week cloritisation. 2% Qz-Carb veinlets and veins (less than 5mm wide). 1% fine disseminated Py	4.90	5.60	206151	0.70	0.052		0.052
5.60	18.00	SY; POR <b>Syenite; Porphyric</b> Redish grenish to purple porphyritic syenite. 3% decimetric to cm rusty fractured segments. Pervasive chlorite-epidote giving grenn color to rock. Partially silicified grey to purple segments. Well developed schistosity (Chl in schisto plans) along lower contact 65TCA. 2% grey-white Qz-Carb veins.  3-5% fine white carbonates veinlets spider web texture							
5.60	18.00	Chl; Sil; Epi <b>Chloritisation; Silicification; Epidotisation</b> Pervasive chlorite-epidote giving grenn color to rock. 10% Partially to totally chloritized feldspars porphyries.  Partially silicified grey to purple segments. 5.6m to 6m 9.9 to 10.6m  3% decimetric to cm rusty fractured segments.							
5.60	18.00	Py <b>Pyrite</b> Fine disseminated Py 1%  Increasing % of Py to 5 % in partially silicified zones 5.6m to 6m 9.9 to 10.6m	5.60	6.00	206152	0.40	0.421		0.421
			6.00	7.50	206153	1.50	0.035		0.035
			7.50	9.00	206154	1.50	0.013		0.013
			9.00	10.50	206155	1.50	0.466		0.466
			10.50	12.00	206156	1.50	0.005		0.005
			12.00	13.50	206157	1.50	0.016		0.016
			13.50	15.00	206158	1.50	<0.005		0.001
			15.00	16.50	206159	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
15.50	18.00	SCH <b>Schistosed</b> Green chlorite in schisto plans well developed near lower contact.	16.50	18.00	206160	1.50	0.011		0.011
18.00	39.00	SY; BX; MNZD <b>Syenite; Breccia; Mineralized</b> Silicified and oxydized upper contact. Grey purple to greenish altered syenite with brecciated segments. 4% grey silica veins. 3% Qz-carbonates pyritized veins-veinlets.							
18.00	39.00	Sil <b>Silicification</b> Partial silicification discoloring rock to grey purple. Silicification is associated with increasing of sulphides content and gold zones.  Strongly chloritized segments: 23.6 to 24.7m Chl-Ep 31.7 to 35.6m Chl							
18.00	39.00	Py <b>Pyrite</b> 18m-18.2m 5% oxydized Py boxwerks  Overall 2 to 5% Disseminated Py. Smalls clusters associated with Si-Qz veins less than 1%	18.00	19.50	206161	1.50	0.876		0.876
			19.50	21.00	206162	1.50	0.251		0.251
			21.00	22.50	206163	1.50	1.180		1.180
			22.50	24.00	206164	1.50	0.682		0.682
			24.00	25.50	206165	1.50	0.028		0.028
			25.50	27.00	206166	1.50	0.660		0.660
			27.00	28.50	206167	1.50	0.594		0.594
			28.50	30.00	206168	1.50	1.435		1.435
			30.00	31.50	206169	1.50	1.685		1.685
			31.50	33.00	206171	1.50	0.317		0.317
			33.00	34.50	206172	1.50	0.029		0.029
			34.50	36.00	206173	1.50	0.349		0.349
			36.00	37.50	206174	1.50	0.527		0.527
			37.50	39.00	206175	1.50	0.234		0.234
39.00	47.50	BX; MNZD <b>Breccia; Mineralized</b> Grey to purple silicified and mineralized breccia (purple to dark grey) alternating with greenish chlorite sericite partially silicified breccia							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		segment						
		Silica+Py and silica-carb veins brecciating the syenite.						
39.00	47.50	Sil						
		<b>Silicification</b>						
		Partial to massive silicification brecciating the syenite and discoloring it to grey purple. Greenish chlorite-sericite patch.						
39.00	47.50	Py	39.00	40.50	206176	1.50	0.223	0.223
		<b>Pyrite</b>	40.50	42.00	206177	1.50	0.060	0.060
		5% fine disseminated Py	42.00	43.50	206178	1.50	0.050	0.050
		45-47m: Py 7-10 % diss, veinlets,	43.50	45.00	206179	1.50	0.749	0.749
			45.00	46.50	206181	1.50	3.280	3.490
			46.50	48.00	206182	1.50	0.857	0.857
47.50	52.40	SY; TZ; FOL; POR						
		<b>Syenite; Transitional Zone; Foliation ; Porphyric</b>						
		Syenite and porphyritic syenite						
		Upper contact marked by well developed schistosity 35 to 60 TCA. Still partially silicified and mineralized purple-grey partially brecciated segments and patch (Si+Py). Strong sericite chlorite in green foliated segments. 2% Spider web texture carbonates veinlets.						
		Fine blackish Py-Si veinlets 2%						
		Rusty fractures toward lower contact 2%. Py breccias 2% in rusty patch.						
		50.6m. Beginning of porphyritic syenite texture (less altered)						
		Rusty sharp lower contact oxidized over 20cm						
47.50	52.40	Chl; Ser; Sil						
		<b>Chloritisation; Sericitisation; Silicification</b>						
		Partially silicified and mineralized purple-grey segments and patch (Si+Py). Strong sericite chlorite in green foliated segments. Green patchy chlorite-sericite. Chloritized to partially chloritized porphyries.						
		5% rusty fractures parallel to schistosity (35 to 60 TCA)						
		45.5m -45.8 massive Si						

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
47.50	50.30	SCH <b>Schistosed</b> chloritized schistosity plans 35 to 60 TCA						
47.50	52.40	Py <b>Pyrite</b> 5%Py in dark purple partially silicified segments. 1-2% disseminated Py in chloritized segments.	48.00	49.50	206183	1.50	0.192	0.192
			49.50	51.00	206184	1.50	0.354	0.354
			51.00	52.50	206185	1.50	0.585	0.585
52.40	102.60	45.5m -47.2 Py 8-10% SY; POR <b>Syenite; Porphyric</b> Redish to green porphyritic syenite. Sharp rusty upper contact. 10% 5mm and + greenish to white feldspars porphyries. Redish very fine grain matrix.  5% thin carbonates spider web texture veinlets. 2% Grey silica-Qz-carbonates veins 2mm to 2cm (sometimes brecciating veins) . 1% black dark green chlorite veinlets. Not mag  Dark purple mineralized and silicified patch ending at 55m  Black to dark green chlorite and mineralized (ex: 70.3m: Py-CP-ML)veinlets  69.35m to 71.7m very fractured core. Chlorite and oxydized veinlets parallel TCA. Slickenside parallel TCA seen in chloritized fractures.  82-86.7m Foliated Chl-Sericite segment.  86.3-86.6m Si breccia						
52.40	102.60	Chl; Ser <b>Chloritisation; Sericitisation</b> Chlorite veinlets and altered porphyries 5% Weak sericite overall but moderate in foliated segments. Partial silicification discoloring host rock to pale redish to grey.						
52.40	102.60	Py; Cp <b>Pyrite ; Chalcopyrite</b> Traces Py disseminated	52.50	54.00	206186	1.50	0.132	0.132
			54.00	55.50	206187	1.50	0.186	0.186
			55.50	57.00	206188	1.50	0.206	0.206

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Traces CP-Malachite	57.00	58.50	206189	1.50		0.065	0.065
			58.50	60.00	206191	1.50		0.006	0.006
		Dark purple mineralized and silicified patch ending at 55m	60.00	61.50	206192	1.50		0.224	0.224
			61.50	63.00	206193	1.50		0.159	0.159
		Black to dark green chlorite and mineralized (ex: 70.3m: Py-CP-ML) veinlets	63.00	64.50	206194	1.50		0.181	0.181
			64.50	66.00	206195	1.50		0.124	0.124
			66.00	67.50	206196	1.50		0.124	0.124
			67.50	69.00	206197	1.50		0.083	0.083
			69.00	70.50	206198	1.50		0.333	0.333
			70.50	72.00	206199	1.50		0.094	0.094
			72.00	73.50	206200	1.50		0.006	0.006
			73.50	75.00	206201	1.50		0.010	0.010
			75.00	76.50	206202	1.50		0.302	0.302
			76.50	78.00	206203	1.50		0.138	0.138
			78.00	79.50	206204	1.50		0.349	0.349
			79.50	81.00	206205	1.50		0.108	0.108
			81.00	82.50	206206	1.50		0.119	0.119
			82.50	84.00	206207	1.50		0.065	0.065
			84.00	85.50	206208	1.50		0.073	0.073
			85.50	87.00	206209	1.50		0.062	0.062
			87.00	88.50	206211	1.50		0.007	0.007
87.80	89.50	BX; BSF	88.50	90.00	206212	1.50		0.024	0.024
		<b>Breccia; Breccia Silicified zone</b>	90.00	91.50	206213	1.50		0.074	0.074
		Silicified pale grey to redish breccia segment. 1% Fine diss Py and disseminated in Chl veinlets	91.50	93.00	206214	1.50		0.014	0.014
			93.00	94.50	206215	1.50		0.049	0.049
			94.50	96.00	206216	1.50		0.005	0.005
			96.00	97.50	206217	1.50		0.035	0.035
			97.50	99.00	206218	1.50		0.057	0.057
			99.00	100.50	206219	1.50		0.035	0.035
			100.50	102.00	206220	1.50		0.027	0.027
			102.00	103.50	206221	1.50		0.057	0.057
102.60	119.65	SY; APH <b>Syenite; Aphanitic</b> Transitionnal brecciated upper contact over .							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
102.60	119.65	<p>Grey redish green aphanitic hydrothermal bleached altered syenite. Blackish mineralized segments. Alt silica and chlorite. 2% chlorite veinlets. Sharp intrusive lower contact.</p> <p>102.6-105m Breccia. Silica-carbonate and chlorite matrix. 2mm to cm syenite clasts. 2% Py fine grain and veinlets</p> <p>Sil; Chl <b>Silicification; Chloritisation</b> Partial Silicification Pervasive chl and veinlets</p>	103.50	105.00	206222	1.50	0.408		0.408
102.60	105.00	<p>Py <b>Pyrite</b> Breccia. 2-3% Py fine grain and veinlets</p>							
105.00	119.65	<p>Py <b>Pyrite</b> over all traces Py</p> <p>dark green to black veins and veinlets 3-4% diss Py: ex: 107.4m , 113.4m , 119.3m</p>	105.00	106.50	206223	1.50	0.258		0.258
			106.50	108.00	206224	1.50	0.006		0.006
			108.00	109.50	206225	1.50	<0.005		0.001
			109.50	111.00	206226	1.50	0.052		0.052
			111.00	112.50	206227	1.50	<0.005		0.001
			112.50	114.00	206228	1.50	0.142		0.142
			114.00	115.50	206229	1.50	0.006		0.006
			115.50	117.00	206231	1.50	0.011		0.011
			117.00	118.50	206232	1.50	0.007		0.007
			118.50	120.00	206233	1.50	0.371		0.371
119.65	126.00	<p>AN; POR <b>Trachyte; Porphyric</b> Sharp upper contact.</p> <p>Greenish redish porphyritic trachyte dyke.</p> <p>3% white beige carbonates spider web texture veinlets 2% grey qz-albite veins</p> <p>Silicified and rusty sharp lower contact From 124.5m to 126m lost about 30cm of core, very fractured</p>							
119.65	126.00	<p>Chl <b>Chloritisation</b> week pervasive Chl</p>							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
119.65	126.00	Py <b>Pyrite</b> 1% disseminated Py 2-3% Py in Qz-albite veins	120.00	121.50	206234	1.50	0.086		0.086
			121.50	123.00	206235	1.50	0.072		0.072
			123.00	124.50	206236	1.50	0.137		0.137
			124.50	126.00	206237	1.50	0.250		0.250
126.00	170.80	SY; APH <b>Syenite; Aphanitic</b> Green to grey and redish dark purple aphanitic strongly altered syenite. Blackish silicified and mineralized segments.  2% chlorite veins and veinlets. end of massive chloritisation at 144m  Beginning of mag at 158.6m ending at 174.5m  2% grey white quartz-albite-carbonates veins							
126.00	144.00	Sil; Chl <b>Silicification; Chloritisation</b> Partial Silicification Pervasive chl and veinlets							
126.00	170.80	Py <b>Pyrite</b> Disseminated and stringers 1% Py  Dark green to black veins and veinlets 3-4% Py diss and veinlets: (ex:129.8 to 130.7m)  159.6-159.8: Py 10% diss and stringers	126.00	127.50	206238	1.50	1.085		1.085
			127.50	129.00	206239	1.50	0.010		0.010
			129.00	130.50	206241	1.50	0.543		0.543
			130.50	132.00	206242	1.50	0.080		0.080
			132.00	133.50	206243	1.50	0.009		0.009
			133.50	135.00	206244	1.50	0.363		0.363
			135.00	136.50	206245	1.50	0.025		0.025
			136.50	138.00	206246	1.50	0.008		0.008
			138.00	139.50	206247	1.50	0.011		0.011
			139.50	141.00	206248	1.50	0.006		0.006
144.00	170.80	Sil; Chl; Ser <b>Silicification; Chloritisation; Sericitisation</b> Partial silicification	141.00	142.50	206249	1.50	0.005		0.005
			142.50	144.00	206251	1.50	<0.005		0.001
			144.00	145.50	206252	1.50	0.024		0.024
			145.50	147.00	206253	1.50	0.802		0.802

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
moderate chloritisation (porphyries and veinlets) Strong chloritisation and sericite 162.7 to 167.3m			147.00	148.50	206254	1.50	0.007	5.38	0.007
			148.50	150.00	206255	1.50	0.235		0.235
			150.00	151.50	206256	1.50	1.460		1.460
			151.50	153.00	206257	1.50	0.098		0.098
			153.00	154.50	206258	1.50	0.012		0.012
			154.50	156.00	206259	1.50	4.810		5.380
			156.00	157.50	206260	1.50	1.770		1.770
			157.50	159.00	206261	1.50	0.579		0.579
			159.00	160.50	206262	1.50	1.275		1.275
			160.50	162.00	206263	1.50	0.020		0.020
			162.00	163.50	206264	1.50	0.012		0.012
			163.50	165.00	206265	1.50	<0.005		0.001
			165.00	166.50	206266	1.50	0.005		0.005
			166.50	168.00	206267	1.50	0.012		0.012
			168.00	169.50	206268	1.50	0.030		0.030
169.50	171.00	206269	1.50	0.007	0.007				
170.80	234.00	SY; POR <b>Syenite; Porphyric</b> Redish to greenish porphyritic syenite. 4% Grey white silica-Qz-carbonates veins and patches 2mm to cm. 1% black dark green chlorite veinlets. Brecciated segments and breccia veins (silica and qz-carb brecciating) . Generally not mag but few segments Mag (ex:221.1-224.9m)  175m-175.2m qz-clacite-(aspyrite)-Py vugs							
170.80	234.00	Chl <b>Chloritisation</b> 5% greenish partailly to totally chloritized feldspars porphyries. 2% chlorite veinlets and chloritized fractures plans.							
170.80	234.00	Py <b>Pyrite</b> 1% disseminated Py in chloritized porphyries and Chl veinlets and Qz-carb veins. 1% disseminated Py in matrix.	171.00	172.50	206271	1.50	0.014	0.014	
			172.50	174.00	206272	1.50	0.005	0.005	
			174.00	175.50	206273	1.50	<0.005	0.001	
			175.50	177.00	206274	1.50	<0.005	0.001	
			177.00	178.50	206275	1.50	<0.005	0.001	

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	178.50	180.00	206276	1.50	0.007		0.007
	180.00	181.50	206277	1.50	<0.005		0.001
	181.50	183.00	206278	1.50	<0.005		0.001
	183.00	184.50	206279	1.50	0.005		0.005
	184.50	186.00	206281	1.50	<0.005		0.001
	186.00	187.50	206282	1.50	0.010		0.010
	187.50	189.00	206283	1.50	0.007		0.007
	189.00	190.50	206284	1.50	0.022		0.022
	190.50	192.00	206285	1.50	0.011		0.011
	192.00	193.50	206286	1.50	<0.005		0.001
	193.50	195.00	206287	1.50	0.026		0.026
	195.00	196.50	206288	1.50	0.061		0.061
	196.50	198.00	206289	1.50	0.037		0.037
	198.00	199.50	206291	1.50	0.052		0.052
	199.50	201.00	206292	1.50	<0.005		0.001
	201.00	202.50	206293	1.50	0.006		0.006
	202.50	204.00	206294	1.50	<0.005		0.001
	204.00	205.50	206295	1.50	<0.005		0.001
	205.50	207.00	206296	1.50	0.018		0.018
	207.00	208.50	206297	1.50	0.005		0.005
	208.50	210.00	206298	1.50	<0.005		0.001
	210.00	211.50	206299	1.50	0.009		0.009
	211.50	213.00	206300	1.50	0.008		0.008
	213.00	214.50	206301	1.50	0.009		0.009
	214.50	216.00	206302	1.50	0.032		0.032
	216.00	217.50	206303	1.50	0.017		0.017
	217.50	219.00	206304	1.50	0.057		0.057
	219.00	220.50	206305	1.50	0.022		0.022
	220.50	222.00	206306	1.50	0.023		0.023
	222.00	223.50	206307	1.50	0.066		0.066
	223.50	225.00	206308	1.50	0.022		0.022
	225.00	226.50	206309	1.50	0.248		0.248
	226.50	228.00	206311	1.50	3.490	3.75	3.750

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	228.00	229.50	206312	1.50	0.629		0.629
	229.50	231.00	206313	1.50	0.042		0.042
	231.00	232.50	206314	1.50	0.028		0.028
	232.50	234.00	206315	1.50	0.024		0.024
234.00	Fin du sondage Nombre d'échantillons : 154 Nombre d'échantillons QAQC : 11 Longueur totale échantillonnée : 229.10						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
30.00	31.50	206170	O53Pb	1.50	0.612	0.612
43.50	45.00	206180	m	1.50	<0.005	0.001
57.00	58.50	206190	O15Pa	1.50	0.976	0.976
85.50	87.00	206210	O50Pb	1.50	0.855	0.855
114.00	115.50	206230	O6Pc	1.50	1.520	1.520
127.50	129.00	206240	m	1.50	<0.005	0.001
141.00	142.50	206250	O53Pb	1.50	0.641	0.641
169.50	171.00	206270	O6Pc	1.50	1.610	1.610
183.00	184.50	206280	m	1.50	<0.005	0.001
196.50	198.00	206290	O53Pb	1.50	0.628	0.628
225.00	226.50	206310	O6Pc	1.50	1.620	1.620

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-91

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : Surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C.Corriveau

Du : 2009-11-16

Date de description : 2009-11-26

Au : 2009-11-19

Collet

UTM

Azimut : 166.80°

Plongée : -44.50°

Longueur : 227.10 m

Est 630 904.2

Nord 5 374 430.6

Élévation 309.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	9.00	169.70°	-44.70°	Non
Reflex	12.00	170.40°	-44.60°	Non
Reflex	15.00	170.60°	-44.50°	Non
Reflex	18.00	169.10°	-44.50°	Non
Reflex	21.00	169.80°	-44.50°	Non
Reflex	24.00	169.80°	-44.40°	Non
Reflex	27.00	169.30°	-44.40°	Non
Reflex	30.00	170.20°	-44.30°	Non
Reflex	33.00	170.10°	-44.40°	Non
Reflex	36.00	170.50°	-44.30°	Non
Reflex	39.00	169.60°	-44.40°	Non
Reflex	42.00	170.90°	-44.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	45.00	170.10°	-44.20°	Non
Reflex	48.00	170.50°	-44.20°	Non
Reflex	51.00	170.80°	-44.20°	Non
Reflex	54.00	171.30°	-44.10°	Non
Reflex	57.00	171.60°	-44.00°	Non
Reflex	60.00	171.90°	-43.90°	Non
Reflex	63.00	170.90°	-43.80°	Non
Reflex	66.00	171.00°	-43.80°	Non
Reflex	69.00	171.60°	-43.60°	Non
Reflex	72.00	171.10°	-43.40°	Non
Reflex	75.00	171.00°	-43.40°	Non
Reflex	78.00	171.30°	-43.40°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All downhole survey corrected 12.5 degrees West

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	81.00	171.80°	-43.20°	Non	Reflex	180.00	179.30°	-42.90°	Non
Reflex	84.00	171.00°	-43.20°	Non	Reflex	183.00	179.40°	-43.00°	Non
Reflex	87.00	171.70°	-43.20°	Non	Reflex	186.00	177.90°	-43.00°	Non
Reflex	90.00	171.90°	-43.90°	Non	Reflex	189.00	177.90°	-43.10°	Non
Reflex	93.00	172.90°	-43.30°	Non	Reflex	192.00	178.50°	-43.00°	Non
Reflex	96.00	171.90°	-43.30°	Non	Reflex	195.00	179.40°	-43.10°	Non
Reflex	99.00	172.10°	-43.30°	Non	Reflex	198.00	179.00°	-43.00°	Non
Reflex	102.00	172.60°	-43.30°	Non	Reflex	201.00	178.60°	-43.10°	Non
Reflex	105.00	173.30°	-43.30°	Non	Reflex	204.00	179.10°	-43.10°	Non
Reflex	108.00	173.00°	-43.40°	Non	Reflex	207.00	178.60°	-42.90°	Non
Reflex	111.00	173.50°	-43.40°	Non	Reflex	210.00	179.90°	-42.90°	Non
Reflex	114.00	173.20°	-43.40°	Non	Reflex	213.00	178.90°	-43.00°	Non
Reflex	117.00	174.00°	-43.40°	Non	Reflex	216.00	179.30°	-43.00°	Non
Reflex	120.00	173.90°	-43.40°	Non	Reflex	219.00	180.00°	-42.90°	Non
Reflex	123.00	175.60°	-43.40°	Non	Reflex	222.00	179.10°	-42.80°	Non
Reflex	126.00	174.70°	-43.20°	Non	Reflex	225.00	180.10°	-42.80°	Non
Reflex	129.00	175.50°	-43.30°	Non	Reflex	227.00	180.50°	-42.80°	Non
Reflex	132.00	175.90°	-43.20°	Non					
Reflex	135.00	175.50°	-43.10°	Non					
Reflex	138.00	174.50°	-43.20°	Non					
Reflex	141.00	175.30°	-43.20°	Non					
Reflex	144.00	175.40°	-43.10°	Non					
Reflex	147.00	175.50°	-43.20°	Non					
Reflex	150.00	176.50°	-43.20°	Non					
Reflex	153.00	176.10°	-43.00°	Non					
Reflex	156.00	176.30°	-43.20°	Non					
Reflex	159.00	176.10°	-43.00°	Non					
Reflex	162.00	176.60°	-43.10°	Non					
Reflex	165.00	177.10°	-43.10°	Non					
Reflex	168.00	176.90°	-42.90°	Non					
Reflex	171.00	177.20°	-42.90°	Non					
Reflex	174.00	177.30°	-42.90°	Non					
Reflex	177.00	177.90°	-42.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.40	MT <b>Overburden</b>						
0.00	24.40	Py <b>Pyrite</b> Fine disseminated Py 1% to traces.  19.3-19.6m 2-4% Py and Py boxwerks in Qx veins.						
3.40	3.90	SY; POR <b>Syenite; Porphyric</b> 3.4m to 3.9m: 50cm of HQ core recuperate from casing. Redish porphyritic syenite. Partially chloritized Fp porphyries.  All core sent to lab for analysis. sample 206316						
3.40	24.40	Chl <b>Chloritisation</b> Moderate to week chloritisation. Fp por partially chloritized. Small blackish chlorite veinlets and fracures filled.  Week silicification toward lower contact.  cpouples rusty fractures (ex 18.3m 30 to 45 TCA)	3.40	3.90	206316	0.50	0.005	0.005
3.90	26.30	SY; POR; POR <b>Syenite; Porphyric; Porphyric</b> Greenish redish to greyish syenite. Fine grain to porphyritic texture depending on level of alteration. 5% thin carbonates spider web texture veinlets. 2% Grey to white silica-Qz-carbonates veins 2mm to cm sometimes brecciating the syenite. Brecciated segmnments whre silica and qz-carb veins are more abundant. Not mag  11.7-12.2m. Small segment breccia. Chlorite matrix with angular matrix supported syenite clasts. Clast mm to cm. Not min	3.90	4.50	206317	0.60	0.006	0.006
			4.50	6.00	206318	1.50	0.007	0.007
			6.00	7.50	206319	1.50	0.014	0.014
			7.50	9.00	206320	1.50	0.055	0.055
			9.00	10.50	206321	1.50	<0.005	0.001
			10.50	12.00	206322	1.50	0.005	0.005
			12.00	13.50	206323	1.50	0.007	0.007
			13.50	15.00	206324	1.50	<0.005	0.001
			15.00	16.50	206325	1.50	0.024	0.024
			16.50	18.00	206326	1.50	<0.005	0.001
			18.00	19.50	206327	1.50	<0.005	0.001
			19.50	21.00	206328	1.50	<0.005	0.001
			21.00	22.50	206329	1.50	0.071	0.071
			22.50	24.00	206331	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
24.40	27.50	Oxy <b>Oxydation</b> Strong pervasive rusty oxydation (limonite).	24.00	25.50	206332	1.50	0.421		0.421
24.40	27.50	FAI <b>Fault</b> Very rusty oxydized broken core. Foliated chloritized sericite segments. Possible fault zone. Upper contact to mineralized zone.							
24.40	34.70	Py <b>Pyrite</b> 2 to 6 % Py fine disseminated and veinlets.	25.50	27.00	206333	1.50	2.050		2.050
26.30	34.70	SY; MNZD; BX <b>Syenite; Mineralized; Breccia</b> Rusty oxydized upper contact. Grey with greenish patch porphyritic mineralized syenite. Grey color cause by partial silicification. Hydrothermal Si+Py alteration brecciating locally. 3% Fine white carbonates spider web veinlets.	27.00	28.50	206334	1.50	1.675		1.675
27.50	34.70	Sil; Chl <b>Silicification; Chloritisation</b> Partial hydrothermal silicification discoloring host rock to purple grey . 10% Chloritized patch, veins and porphyries.	28.50	30.00	206335	1.50	2.020		2.020
			30.00	31.50	206336	1.50	1.880		1.880
			31.50	33.00	206337	1.50	3.400	3.29	3.290
			33.00	34.50	206338	1.50	0.200		0.200
			34.50	36.00	206339	1.50	0.286		0.286
34.70	45.30	SY <b>Syenite</b> Greenish purple to grey very altered and fractured syenite. Few mineralized veinlets. Brecciated Si-Carb veins.							
34.70	45.30	Chl <b>Chloritisation</b> Moderate chlorite and sericite greenish pervasive alteration							
34.70	45.30	Py <b>Pyrite</b> 1% pyrite veinlets and disseminated	36.00	37.50	206341	1.50	0.020		0.020
			37.50	39.00	206342	1.50	0.268		0.268
			39.00	40.50	206343	1.50	1.235		1.235
			40.50	42.00	206344	1.50	0.679		0.679

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
45.30	55.25	BX; I2D; BR; MNZD <b>Breccia; Syenite; Brecciated; Mineralized</b> Purple Grey with greenish patch mineralized brecciated syenite. Grey color cause by partial silicification. Hydrothermal Si+Py alteration brecciating. 3% Fine white carbonates spider web veinlets.  52.4-52.6m. Qz-Si veins. 1-2% Hm veinlets and diss, 2% fine py diss.  Transitionnal lower contact..silicification out.	42.00	43.50	206345	1.50	0.496		0.496
			43.50	45.00	206346	1.50	0.114		0.114
			45.00	46.50	206347	1.50	0.180		0.180
45.30	55.25	Sil; Chl; Ser <b>Silicification; Chloritisation; Sericitisation</b> Partial to massive silicification brecciating and discoloring the syenite. Chloritized and sericitized greenish patch							
45.30	55.25	Py; Hm <b>Pyrite ; Hematite</b> 5 % fine disseminated Py. 1% small Py clusters and veinlets.  HM traces diss and veinlets Possible very fine grain AsPy  52.4-52.6m. Qz-Si veins. 1-2% Hm veinlets and diss, 2% fine py diss.	46.50	48.00	206348	1.50	0.243		0.243
			48.00	49.50	206349	1.50	0.490		0.490
			49.50	51.00	206351	1.50	1.210		1.210
			51.00	52.50	206352	1.50	2.910		2.910
			52.50	54.00	206353	1.50	2.320		2.320
			54.00	55.50	206354	1.50	0.590		0.590
55.25	116.50	SY; POR <b>Syenite; Porphyric</b> Redish with greenish patch porphyritic syenite. 5-10% 5mm+ white to greenish feldspars porphyries. 2-3% black to green chlorite veinlets and 2-3% greenish sericite veinlets sometime brecciating the syenite. 2% Grey silica-Qz-carbonates veins 2mm to cm. 3% white carbonates veinlets spider web texture.  Disseminated magnetite and in veinlets. Weak to moderate magnetic.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
55.25	116.50	<p>64.1m- 64.4m chloritized matrix breccia veins. Parallel to 30 degrees TCA. 3% 5mm Py clusters.</p> <p>85.7m-87.7m Strongly chloritized and sericitized segment. 2-3% Py diss. 5% white grey Qz-Carb-Albite veins all directions.</p> <p>Chl; Ser <b>Chloritisation; Sericitisation</b> 5% pervasive Chlorite 2-3% black to green chlorite veinlets and 2-3% greenish sericite veinlets.</p>							
55.25	116.50	<p>85.7m-87.7m Strongly chloritized and sericitized segment Py; Cp; Hm; As <b>Pyrite ; Chalcopyrite ; Hematite ; Arsenopyrite</b> Erratic distribution of about 1% disseminated and clusters of fine grain Py</p> <p>1% Hm and Cp and ArsPy disseminated in Carbonates rich veins.</p> <p>85.7m-87.7m Strongly chloritized and sericitized segment. 2-3% Py diss. 5% white grey Qz-Carb-Albite veins all directions.</p>	55.50	57.00	206355	1.50	0.409		0.409
			57.00	58.50	206356	1.50	0.320		0.320
			58.50	60.00	206357	1.50	0.330		0.330
			60.00	61.50	206358	1.50	0.153		0.153
			61.50	63.00	206359	1.50	0.008		0.008
			63.00	64.50	206360	1.50	<0.005		0.001
			64.50	66.00	206361	1.50	0.019		0.019
			66.00	67.50	206362	1.50	0.009		0.009
			67.50	69.00	206363	1.50	0.006		0.006
			69.00	70.50	206364	1.50	0.032		0.032
			70.50	72.00	206365	1.50	0.028		0.028
			72.00	73.50	206366	1.50	0.055		0.055
			73.50	75.00	206367	1.50	0.231		0.231
			75.00	76.50	206368	1.50	0.124		0.124
			76.50	78.00	206369	1.50	0.006		0.006
			78.00	79.50	206371	1.50	0.005		0.005
			79.50	81.00	206372	1.50	0.053		0.053
			81.00	82.50	206373	1.50	0.301		0.301
			82.50	84.00	206374	1.50	3.950	3.94	3.940
			84.00	85.50	206375	1.50	0.337		0.337
			85.50	87.00	206376	1.50	0.052		0.052

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
90.20	90.80	VEI;CcClQz;T;10°;As03Cp02Hm03; <b>Vein Calcite Chlorite Quartz Tension 10°</b> <b>Arsenopyrite03% Chalcopyrite02% Hematite03%</b> Chlorite Qz-Calcite breccia veins. Vugs. Cp clusters diss 1-2%. Fine arsenopyrite disseminated clusters 3%. Hematite speculaire with striation 3%	87.00	88.50	206377	1.50	0.075		0.075
			88.50	90.00	206378	1.50	0.025		0.025
			90.00	91.50	206379	1.50	0.023		0.023
			91.50	93.00	206381	1.50	0.128		0.128
			93.00	94.50	206382	1.50	0.109		0.109
			94.50	96.00	206383	1.50	0.112		0.112
			96.00	97.50	206384	1.50	0.086		0.086
			97.50	99.00	206385	1.50	0.023		0.023
			99.00	100.50	206386	1.50	0.033		0.033
			100.50	102.00	206387	1.50	0.049		0.049
			102.00	103.50	206388	1.50	0.035		0.035
			103.50	105.00	206389	1.50	<0.005		0.001
			105.00	106.50	206391	1.50	0.010		0.010
			106.50	108.00	206392	1.50	0.017		0.017
			108.00	109.50	206393	1.50	<0.005		0.001
			109.50	111.00	206394	1.50	<0.005		0.001
114.40	114.50	VEI;2;CcAk;T;25°;Cp01Hm01As01; <b>Vein 2 Calcite Ankerite Tension 25° Chalcopyrite01%</b> <b>Hematite01% Arsenopyrite01%</b> 2cm wide calcite ankerite vein. 3% sulphides disseminated Hm-Cp-AsPy	111.00	112.50	206395	1.50	<0.005		0.001
			112.50	114.00	206396	1.50	<0.005		0.001
			114.00	115.50	206397	1.50	0.300		0.300
			115.50	117.00	206398	1.50	0.183		0.183
116.50	129.65	SY; TZ <b>Syenite; Transition zone</b> Green to grey and redish dark purple aphanitic strongly altered leached syenite.  3% grey Qz veins all directions.  Blackish silicified and mineralized segments.							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
116.50	129.65	Ser; Chl <b>Sericitisation; Chloritisation</b> Strongly sicitized and chloritized leaching. Partially silicified						
116.50	129.65	Py <b>Pyrite</b> 1% disseminated fine brassy to blackish altered Py.	117.00	118.50	206399	1.50	0.018	0.018
			118.50	120.00	206400	1.50	0.099	0.099
			120.00	121.50	206401	1.50	0.537	0.537
		121.2m to 121.4m Grey Qz brecciated vein. 1% Py in vein. 5% fine Py over 3 cm at bottom margin	121.50	123.00	206402	1.50	0.020	0.020
			123.00	124.50	206403	1.50	0.173	0.173
			124.50	126.00	206404	1.50	0.014	0.014
		123 to 123.5m Blackish dark green segment sericite-chlorite 5-8% disseminated Py in matrix.	126.00	127.50	206405	1.50	0.007	0.007
			127.50	129.00	206406	1.50	0.016	0.016
			129.00	130.50	206407	1.50	0.345	0.345
129.65	136.50	AN; POR <b>Trachyte; Porphyric</b> Redish to greenish with 40 % whitish feldspars porphyries trachytic dyke. Upper and lower sharp cooked contact margin. 3% white carbonates spider web texture veinlets. 8% green sericite chlorite veinlets.						
129.65	136.50	Ser; Chl <b>Sericitisation; Chloritisation</b> * % green sericite chlorites veinlets and in matrix						
129.65	136.50	Py <b>Pyrite</b> Traces of brassy fine to medium grains disseminated Py	130.50	132.00	206408	1.50	0.079	0.079
			132.00	133.50	206409	1.50	0.011	0.011
			133.50	135.00	206411	1.50	0.092	0.092
			135.00	136.50	206412	1.50	0.266	0.266
136.50	183.70	SY; APH; MNZD <b>Syenite; Aphanitic; Mineralized</b> Fine grain to aphanitic very altered redish grey to green mineralized syenite. Mineralization up to 10% fine to medium grain Py when rock get moderate to dark grey and silicified (also in some chloritized segments)  Partially silicified and brecciated segments 160.3-161.3m Strong to massive silicified mineralized breccia. Chl-Sericite fractures with slickensides.						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
136.50	183.70	<p>3% blackish to dark green chlorite veinlets. 2% Qz-carb veins 2mm to 2cm</p> <p>180.7 chl fracture with slickensides 40TCA</p> <p>178.5 to 183.7m. Brecciated lower contact. Syenite angular clasts mm to cm. Chlorite-Sericete-calcite (Qz) stockwerks and veins brecciating. Mineralized breccia veins margins, fluidal pyrite stringers and disseminated in breccia matrix. 183.2-183.9m 1-2% vugs in Carb-Qz veins</p> <p>Sil; Chl; Ser <b>Silicification; Chloritisation; Sericitisation</b> Partial pervasive silicification discoloring syenite. Massive silicification 160.3m to 161.3m 5-15% Chloritized and sericitized veinlets and patches giving more green color to host rock</p> <p>178.5-183.7m moderate to strong sericitization and chloritization breccia matrix.</p>							
136.50	183.70	<p>Py; Cp <b>Pyrite ; Chalcopyrite</b> Erratic pyrite distribution 1% to 10% Mineralization up to 10% fine grain Py when rock get moderate to dark grey in partially silicified segments. In mineralized segments, 1% fine Py stringers and disseminated or in veins. 1% Cp clusters in veins or ion masses with Py.</p> <p>(ex: 137.6m to 139m: 10% Py diss and veinlets, also 147.8 to 149m)</p> <p>Traces Chalcopyrite clusters in chloritized blackish veinlets</p> <p>178.5 to 183.7m. Brecciated lower contact. Mineralized breccia veins margins 5%Py, fluidal pyrite stringers and disseminated in breccia matrix. 183.2-183.9m 1-2% vugs in Carb-Qz veins 2% Py</p>	136.50	138.00	206413	1.50	0.122	4.21	0.122
			138.00	139.50	206414	1.50	1.785		1.785
			139.50	141.00	206415	1.50	0.034		0.034
			141.00	142.50	206416	1.50	0.010		0.010
			142.50	144.00	206417	1.50	0.166		0.166
			144.00	145.50	206418	1.50	0.190		0.190
			145.50	147.00	206419	1.50	2.620		2.620
			147.00	148.50	206420	1.50	1.815		1.815
			148.50	150.00	206421	1.50	4.290		4.210
			150.00	151.50	206422	1.50	0.033		0.033
			151.50	153.00	206423	1.50	1.050		1.050
			153.00	154.50	206424	1.50	0.283		0.283
			154.50	156.00	206425	1.50	0.627		0.627
			156.00	157.50	206426	1.50	0.791		0.791
			157.50	159.00	206427	1.50	0.618	0.618	
			159.00	160.50	206428	1.50	0.017	0.017	
			160.50	162.00	206429	1.50	1.635	1.635	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
183.70	227.10	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic syenite. 20% 2cm or less feldspars porphyries. Weak to strongly magnetic segments. 5% white carbonates veinlets spider web texture 1-2% blackish to dark green chlorite veinlets all directions.  3-5% fine grain beige orange leucoxene  3% qz-carb (dolomite-calcite and ankerite) veins usually 40TCA.	162.00	163.50	206431	1.50	1.605	3.41	1.605
			163.50	165.00	206432	1.50	0.007		0.007
			165.00	166.50	206433	1.50	1.330		1.330
			166.50	168.00	206434	1.50	0.033		0.033
			168.00	169.50	206435	1.50	3.500		3.410
			169.50	171.00	206436	1.50	1.060		1.060
			171.00	172.50	206437	1.50	0.333		0.333
			172.50	174.00	206438	1.50	0.256		0.256
			174.00	175.50	206439	1.50	1.025		1.025
			175.50	177.00	206441	1.50	0.008		0.008
			177.00	178.50	206442	1.50	1.115		1.115
			178.50	180.00	206443	1.50	0.411		0.411
			180.00	181.50	206444	1.50	0.552		0.552
			181.50	183.00	206445	1.50	0.117		0.117
			183.00	184.50	206446	1.50	0.014		0.014
183.70	227.10	Ser; Chl <b>Sericitisation; Chloritisation</b> 4% fibrous and veinlets of yellowish sericite  5% Fp porphyries partially to totally chloritized	184.50	186.00	206447	1.50	0.030	0.030	
			186.00	187.50	206448	1.50	0.005	0.005	
183.70	227.10	Py; Hm <b>Pyrite ; Hematite</b> 1% disseminated Py 1% 1cm or less Py clusters and Hm clusters in Qz-Carb veins (200.7m) or in chloritized-sericitized margins	187.50	189.00	206449	1.50	0.042	0.042	
			189.00	190.50	206451	1.50	0.029	0.029	
			190.50	192.00	206452	1.50	<0.005	0.001	
			192.00	193.50	206453	1.50	0.050	0.050	
		190.9m 1to 5mm specular hematite vein 35 to 40TCA							

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
226.1m 1cm Qz-carb 5% Spec hematite clusters and diss	193.50	195.00	206454	1.50	0.062		0.062
	195.00	196.50	206455	1.50	0.044		0.044
226.2-226.4m Si-Hm-(Aspy)-Py brecciating veins 25-30TCA	196.50	198.00	206456	1.50	0.025		0.025
	198.00	199.50	206457	1.50	0.007		0.007
	199.50	201.00	206458	1.50	0.015		0.015
	201.00	202.50	206459	1.50	0.032		0.032
	202.50	204.00	206460	1.50	0.022		0.022
	204.00	205.50	206461	1.50	0.033		0.033
	205.50	207.00	206462	1.50	0.016		0.016
	207.00	208.50	206463	1.50	0.015		0.015
	208.50	210.00	206464	1.50	<0.005		0.001
	210.00	211.50	206465	1.50	<0.005		0.001
	211.50	213.00	206466	1.50	0.011		0.011
	213.00	214.50	206467	1.50	0.005		0.005
	214.50	216.00	206468	1.50	0.008		0.008
	216.00	217.50	206469	1.50	0.044		0.044
	217.50	219.00	206471	1.50	0.010		0.010
219.00	220.50	206472	1.50	0.039		0.039	
220.50	222.00	206473	1.50	0.005		0.005	
222.00	223.50	206474	1.50	0.035		0.035	
223.50	225.00	206475	1.50	0.011		0.011	
225.00	226.50	206476	1.50	0.054		0.054	
226.50	227.10	206477	0.60	0.007		0.007	
227.10	Fin du sondage Nombre d'échantillons : 151 Nombre d'échantillons QAQC : 11 Longueur totale échantillonnée : 223.70						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
21.00	22.50	206330	O54Pa	1.50	2.950	2.950
34.50	36.00	206340	m	1.50	0.006	0.006
48.00	49.50	206350	O61d	1.50	4.880	4.890
76.50	78.00	206370	O53Pb	1.50	0.620	0.620
90.00	91.50	206380	m	1.50	<0.005	0.001
103.50	105.00	206390	O15Pa	1.50	0.983	0.983
132.00	133.50	206410	O50Pb	1.50	0.860	0.860
160.50	162.00	206430	O6Pc	1.50	1.610	1.610
174.00	175.50	206440	m	1.50	<0.005	0.001
187.50	189.00	206450	O50Pb	1.50	0.864	0.864
216.00	217.50	206470	O15Pa	1.50	0.848	0.848

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-92

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C.Gagnier

Du : 2009-11-13

Date de description : 2009-11-29

Au : 2009-11-16

Collet

Azimut : 178.13°  
 Plongée : -55.20°  
 Longueur : 237.00 m

UTM

Est	630 901.7
Nord	5 374 451.2
Élévation	308.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	212.60°	-87.10°	Oui
Reflex	0.00	212.60°	-87.10°	Oui
Reflex	15.00	170.00°	-55.00°	Oui
Reflex	18.00	179.90°	-55.50°	Non
Reflex	21.00	180.40°	-55.40°	Non
Reflex	24.00	180.30°	-55.40°	Non
Reflex	27.00	184.60°	-55.40°	Oui
Reflex	30.00	181.30°	-55.40°	Non
Reflex	33.00	180.50°	-55.40°	Non
Reflex	36.00	188.60°	-53.80°	Oui
Reflex	39.00	180.90°	-55.40°	Non
Reflex	42.00	181.20°	-55.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	45.00	182.30°	-55.30°	Non
Reflex	48.00	182.90°	-55.20°	Non
Reflex	51.00	183.80°	-55.20°	Non
Reflex	54.00	183.50°	-55.10°	Non
Reflex	57.00	181.40°	-55.10°	Non
Reflex	60.00	181.20°	-54.80°	Non
Reflex	63.00	181.70°	-55.10°	Non
Reflex	66.00	183.30°	-55.10°	Non
Reflex	69.00	181.30°	-55.10°	Non
Reflex	72.00	181.90°	-55.00°	Non
Reflex	75.00	181.70°	-55.00°	Non
Reflex	78.00	180.80°	-55.00°	Non

Description

GPS Datum NAD83, UTM Zone 17.

The single-shot and multi-shot Reflex tests were corrected for magnetic declination (12.5 degrees to the west). Hole surveyed Nov 2009 by Descarreaux.

The portion between the RW zone and the RS zone have been quarter split and sent for metallurgical tests.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	81.00	181.50°	-55.00°	Non	Reflex	180.00	182.50°	-53.90°	Non
Reflex	84.00	181.70°	-55.00°	Non	Reflex	183.00	183.30°	-54.20°	Non
Reflex	87.00	180.70°	-55.00°	Non	Reflex	186.00	183.20°	-54.20°	Non
Reflex	90.00	181.50°	-54.70°	Non	Reflex	189.00	183.80°	-54.10°	Non
Reflex	93.00	181.80°	-54.90°	Non	Reflex	192.00	183.80°	-54.10°	Non
Reflex	96.00	181.90°	-54.90°	Non	Reflex	195.00	183.70°	-54.00°	Non
Reflex	99.00	181.90°	-54.90°	Non	Reflex	198.00	183.90°	-54.00°	Non
Reflex	102.00	182.40°	-54.90°	Non	Reflex	201.00	184.00°	-54.10°	Non
Reflex	105.00	181.60°	-54.80°	Non	Reflex	204.00	184.00°	-54.00°	Non
Reflex	108.00	182.20°	-54.90°	Non	Reflex	207.00	183.10°	-54.00°	Non
Reflex	111.00	181.80°	-54.90°	Non	Reflex	210.00	184.70°	-53.70°	Non
Reflex	114.00	181.90°	-54.70°	Non	Reflex	213.00	184.70°	-53.70°	Non
Reflex	117.00	182.30°	-54.80°	Non	Reflex	216.00	184.50°	-53.70°	Non
Reflex	120.00	182.90°	-54.70°	Non	Reflex	219.00	183.50°	-53.40°	Non
Reflex	123.00	181.90°	-54.80°	Non	Reflex	222.00	183.70°	-53.50°	Non
Reflex	126.00	182.30°	-54.80°	Non	Reflex	225.00	184.80°	-53.30°	Non
Reflex	129.00	182.70°	-54.70°	Non	Reflex	228.00	184.00°	-53.40°	Non
Reflex	132.00	182.80°	-54.70°	Non	Reflex	231.00	184.60°	-53.50°	Non
Reflex	135.00	182.80°	-54.60°	Non	Reflex	234.00	184.30°	-53.40°	Non
Reflex	138.00	182.00°	-54.50°	Non	Reflex	237.00	185.20°	-53.40°	Non
Reflex	141.00	183.00°	-54.50°	Non					
Reflex	144.00	182.80°	-54.50°	Non					
Reflex	147.00	182.80°	-54.40°	Non					
Reflex	150.00	182.80°	-54.20°	Non					
Reflex	153.00	183.60°	-54.30°	Non					
Reflex	156.00	183.30°	-54.40°	Non					
Reflex	159.00	183.70°	-54.30°	Non					
Reflex	162.00	182.90°	-54.30°	Non					
Reflex	165.00	183.50°	-54.20°	Non					
Reflex	168.00	183.70°	-54.30°	Non					
Reflex	171.00	182.80°	-54.20°	Non					
Reflex	174.00	183.30°	-54.20°	Non					
Reflex	177.00	183.60°	-54.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT <b>overburden</b> Casing to 3m.						
3.00	78.60	SY; POR <b>Syenite; Porphyric</b> Red brick, mottled syenite with less than 5% of 0.5 to 1cm anhedral pinkish , often chloritized feldspar phenocrystals in an aphanitic, not magnetic matrix. Cross-cutted by 2% of colorless to white millimetric quartz-feldspar (and locally black tourmaline) veinlets generally at 50 TCA. Gradational lower contact over 30cm.	3.00	4.50	212650	1.50	0.110	0.110
			4.50	6.00	212651	1.50	0.030	0.030
			6.00	7.50	212652	1.50	0.018	0.018
			7.50	9.00	212653	1.50	0.020	0.020
			9.00	10.50	212654	1.50	0.191	0.191
3.00	10.50	Wea <b>Weathering (Incl. Saprolitic alter.)</b> Brown hematization along the fractures.						
10.50	24.30	Chl <b>Chloritisation</b> Weak chloritization.	10.50	12.00	212656	1.50	0.014	0.014
			12.00	13.50	212657	1.50	0.081	0.081
			13.50	15.00	212658	1.50	0.045	0.045
			15.00	16.50	212659	1.50	0.023	0.023
			16.50	18.00	212661	1.50	0.006	0.006
			18.00	19.50	212662	1.50	<0.005	0.001
			19.50	21.00	212663	1.50	0.005	0.005
			21.00	22.50	212664	1.50	0.015	0.015
			22.50	24.00	212665	1.50	0.010	0.010
			24.00	25.50	212666	1.50	0.010	0.010
			25.50	27.00	212667	1.50	0.005	0.005
			27.00	28.50	212668	1.50	0.006	0.006
			28.50	30.00	212669	1.50	<0.005	0.001
			30.00	31.50	212670	1.50	0.317	0.317
			31.50	33.00	212671	1.50	0.109	0.109
			33.00	34.50	212672	1.50	0.010	0.010
			34.50	36.00	212673	1.50	0.018	0.018
			36.00	37.50	212674	1.50	0.012	0.012
			37.50	39.00	212676	1.50	0.008	0.008
38.80	46.60	Ser; Chl <b>Sericitisation; Chloritisation</b> Apple-green alteration related to quartz veins at 80 TCA.	39.00	40.50	212677	1.50	0.012	0.012

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
38.80	45.10	Foliated at 50 TCA. FOL Foliation 50°						
39.15	39.25	VEI;10;Qz;;80°;00; Vein 10 Quartz 80° 00% 10cm white quartz vein at 80 TCA. Not mineralized.	40.50	42.00	212678	1.50	0.006	0.006
			42.00	43.50	212679	1.50	0.006	0.006
			43.50	45.00	212681	1.50	0.055	0.055
44.50	46.60	Py0.5 Pyrite 0.5% Medium size (0.25 to 0.5mm diameter) euhedral pyrite.	45.00	46.50	212682	1.50	0.045	0.045
			46.50	48.00	212683	1.50	<0.005	0.001
			48.00	49.50	212684	1.50	0.005	0.005
			49.50	51.00	212685	1.50	<0.005	0.001
			51.00	52.50	212686	1.50	<0.005	0.001
			52.50	54.00	212687	1.50	0.007	0.007
			54.00	55.50	212688	1.50	<0.005	0.001
			55.50	57.00	212689	1.50	<0.005	0.001
			57.00	58.50	212690	1.50	0.029	0.029
			58.50	60.00	212691	1.50	<0.005	0.001
			60.00	61.50	212692	1.50	0.008	0.008
			61.50	63.00	212693	1.50	0.038	0.038
			63.00	64.50	212694	1.50	0.557	0.557
			64.50	66.00	212696	1.50	0.321	0.321
			66.00	67.50	212697	1.50	0.005	0.005
			67.50	69.00	212698	1.50	0.015	0.015
			69.00	70.50	212699	1.50	0.051	0.051
			70.50	72.00	212701	1.50	0.111	0.111
			72.00	73.50	212702	1.50	0.648	0.648
			73.50	75.00	212703	1.50	0.768	0.768
			75.00	76.50	212704	1.50	0.178	0.178
			76.50	78.00	212705	1.50	0.076	0.076
			78.00	79.50	212706	1.50	0.596	0.596
44.50	44.54	VEI;4;;;80°;00; Vein 4 80° 00% A 4cm white quartz vein at 80 TCA.						
78.60	90.00	SY POR; MNZ Syenite Porphyry Intrusive; Mineralized	79.50	81.00	212707	1.50	0.964	0.964

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
RW ZONE. Gradational upper contacts over 30cm. Grey to greenish mineralized porphyry syenite. Strongly silicified, moderately sericitized and carbonatized. Mineralized with 0.3% to 4% of fine pyrite. The white anhedral feldspar phenocrysts amount to 5% to 40% (3mm to 10mm; average of 6mm) but are sometimes blurred and difficult to see. This is a multi-phase syenite : several generations of intrusions are involved as revealed by the different characteristics observed (differences in the phenocrysts content, in the alteration, in the mineralisation, etc). Locally brecciated (hydrothermal breccia). Cross-cut by 2% of millimetric, white quartz-carbonate veinlets at 60 TCA.			81.00	82.50	212708	1.50	2.740		2.740
			82.50	84.00	212709	1.50	2.620		2.620
			84.00	85.50	212710	1.50	0.854		0.854
			85.50	87.00	212711	1.50	0.176		0.176
			87.00	88.50	212712	1.50	0.833		0.833
			88.50	90.00	212713	1.50	0.587		0.587
78.60	87.70	Sil; Ser; Car <b>Silicification; Sericitisation; Carbonatisation</b>							
78.60	87.70	BRE <b>Breccia</b> Hydrothermal breccia.							
78.60	87.70	Py02 <b>Pyrite 02%</b> From 0.3 to 4% of fine pyrite.							
90.00	130.70	SY <b>Syenite</b> Gradational upper contacts over 30cm. Red to locally lightly greenish mottled , massive syenite with less than 1% of subhedral white to cream, 3-10mm (average: 6mm) feldspar phenocrysts. Locally weakly magnetic. Locally weakly magnetic.Cross-cut by less than 1% of millimetric dark green carbonate-chlorite veinlets at 30 TCA and white quartz-carbonate 1-5cm veins at 60 TCA.	90.00	92.00	212714	2.00	0.061		0.061
			92.00	94.00	212716	2.00	0.243		0.243
92.10	92.15	VEI;QzCb;;55°; <b>Vein Quartz Carbonate 55°</b> A 5cm white to pinkish quartz-carbonate veins at 55 TCA.							
93.85	93.90	VEI;5;QzCl;;60°; <b>Vein 5 Quartz Chlorite 60°</b> A 5cm quartz-chlorite vein at 60 TCA.	94.00	96.00	212717	2.00	0.181		0.181
			96.00	98.00	212718	2.00	0.282		0.282
			98.00	100.00	212719	2.00	0.182		0.182
			100.00	102.00	212721	2.00	0.231		0.231
			102.00	104.00	212722	2.00	0.136		0.136
			104.00	106.00	212723	2.00	0.238		0.238
			106.00	108.00	212724	2.00	0.068		0.068
108.00	110.00	212725	2.00	0.284		0.284			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
111.30	112.50	Chl <b>Chloritisation</b> Apple-green chloritisation/sericitization.	110.00	112.00	212726	2.00	0.500		0.500
111.95	112.05	VEI;10;Qz;;80°;; <b>Vein 10 Quartz 80°</b> 80% white quartz over 10cm (at 80 TCA).	112.00	114.00	212727	2.00	0.050		0.050
			114.00	116.00	212728	2.00	0.079		0.079
			116.00	118.00	212729	2.00	0.027		0.027
			118.00	120.00	212730	2.00	0.007		0.007
			120.00	122.00	212731	2.00	0.037		0.037
122.00	129.30	Chl <b>Chloritisation</b>	122.00	124.00	212732	2.00	0.114		0.114
			124.00	126.00	212733	2.00	0.075		0.075
			126.00	128.00	212734	2.00	0.122		0.122
			128.00	130.70	212736	2.70	0.517		0.517
122.00	126.00	FOL <b>Foliation 40°</b> Locally weakly foliated at 40 TCA (greenish chlorite laminas).							
130.70	203.00	SY; MNZ <b>Syenite; Mineralized</b> RS ZONE. Gradational upper contact over 30cm. Grey to locally yellowish multi-phase syenite, strongly silicified, moderately sericitized and carbonatized. Mineralized with 0.2 to up to 5% of fine pyrite (average: 2%). Cross-cut by 1% of 3mm-6mm colorless quartz and white feldspar of carbonate veinlets at variable angle (but often between 45 and 80 TCA). Sharp intrusive contact at 40 TCA.							
130.70	203.00	Sil; Ser; Car <b>Silicification; Sericitisation; Carbonatisation</b> Strongly silicified. Moderately sericitized and carbonatized.							
130.70	192.40	BRE <b>Breccia</b> Locally brecciated.							
130.70	203.00	Py02 <b>Pyrite 02%</b> RS mineralized zone. Between 0.2 and 5% of fine pyrite (average: 2%).	130.70	132.00	212737	1.30	4.210	4.28	4.280
			132.00	133.50	212738	1.50	0.499		0.499
			133.50	135.00	212739	1.50	0.439		0.439
			135.00	136.50	212741	1.50	0.802		0.802
			136.50	138.00	212742	1.50	3.030	3.71	3.710
			138.00	139.50	212743	1.50	2.010		2.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	139.50	141.00	212744	1.50	3.270	3.40	3.400
	141.00	142.50	212745	1.50	2.230		2.230
	142.50	144.00	212746	1.50	5.170	4.53	4.530
	144.00	145.50	212747	1.50	3.250	3.39	3.390
	145.50	147.00	212748	1.50	5.480	5.46	5.460
	147.00	148.50	212749	1.50	6.150	5.78	5.780
	148.50	150.00	212750	1.50	4.950	4.93	4.930
	150.00	151.50	212751	1.50	3.110	3.24	3.240
	151.50	153.00	212752	1.50	2.870		2.870
	153.00	154.50	212753	1.50	2.530		2.530
	154.50	156.00	212754	1.50	1.240		1.240
	156.00	157.50	212756	1.50	0.972		0.972
	157.50	159.00	212757	1.50	1.900		1.900
	159.00	160.50	212758	1.50	2.470		2.470
	160.50	162.00	212759	1.50	2.550		2.550
	162.00	163.50	212761	1.50	1.860		1.860
	163.50	165.00	212762	1.50	0.689		0.689
	165.00	166.50	212763	1.50	2.280		2.280
	166.50	168.00	212764	1.50	1.030		1.030
	168.00	169.50	212765	1.50	1.325		1.325
	169.50	171.00	212766	1.50	1.445		1.445
	171.00	172.50	212767	1.50	0.099		0.099
	172.50	174.00	212768	1.50	0.292		0.292
	174.00	175.50	212769	1.50	1.815		1.815
	175.50	177.00	212770	1.50	0.617		0.617
	177.00	178.50	212771	1.50	5.000	5.04	5.040
	178.50	180.00	212772	1.50	8.420	8.42	8.420
	180.00	181.50	212773	1.50	2.160		2.160
	181.50	183.00	212774	1.50	0.348		0.348
	183.00	184.50	212776	1.50	0.407		0.407
	184.50	186.00	212777	1.50	2.340		2.340
	186.00	187.50	212778	1.50	0.500		0.500
	187.50	189.00	212779	1.50	3.100	2.99	2.990



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
203.00	237.00	GA <b>Gabbro</b> Sharp intrusive upper contact at 40 TCA. Medium to dark green, strongly chloritized dolerite (fine grained gabbro; average of the grain: 0.5mm). 1-2% of smaller than 1mm yellow leucoxene shards. The first 3m of the unit shows a transitional zone: yellow, aphanitic strongly sericitic.  EOH : 237m	189.00	190.50	212781	1.50	2.360		2.360
			190.50	192.00	212782	1.50	3.740	3.71	3.710
			192.00	193.50	212783	1.50	1.590		1.590
			193.50	195.00	212784	1.50	3.980	3.96	3.960
			195.00	196.50	212785	1.50	4.800	4.79	4.790
			196.50	198.00	212786	1.50	1.280		1.280
			198.00	199.50	212787	1.50	0.159	0.20	0.200
			199.50	201.00	212788	1.50	0.128	0.30	0.300
			201.00	203.00	212789	2.00	1.185	2.60	2.600
			203.00	205.00	212790	2.00	0.219		0.219
			205.00	207.00	212791	2.00	0.053		0.053
			207.00	208.50	212792	1.50	0.005		0.005
			208.50	210.00	212793	1.50	<0.005		0.001
			210.00	211.50	212794	1.50	<0.005		0.001
			211.50	213.00	212796	1.50	<0.005		0.001
			213.00	214.50	212797	1.50	<0.005		0.001
			214.50	216.00	212798	1.50	0.011		0.011
			216.00	217.50	212799	1.50	0.050		0.050
			217.50	219.00	212801	1.50	0.009		0.009
			219.00	220.50	212802	1.50	<0.005		0.001
220.50	222.00	212803	1.50	<0.005		0.001			
222.00	223.50	212804	1.50	<0.005		0.001			
223.50	225.00	212805	1.50	<0.005		0.001			
225.00	226.50	212806	1.50	0.006		0.006			
226.50	228.00	212807	1.50	<0.005		0.001			
228.00	229.50	212808	1.50	<0.005		0.001			
229.50	231.00	212809	1.50	<0.005		0.001			
231.00	232.50	212810	1.50	<0.005		0.001			
232.50	234.00	212811	1.50	<0.005		0.001			
234.00	235.50	212812	1.50	0.005		0.005			
203.00	213.70	Chi <b>Chloritisation</b> Strong pervasive chloritisation.							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
203.00	213.70	FOL Foliation 40°						
237.00	Fin du sondage Nombre d'échantillons : 147 Nombre d'échantillons QAQC : 16 Longueur totale échantillonnée : 232.50							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.50	10.50	212655	O6Pc	0.00	1.565	1.565
16.50	16.50	212660	m	0.00	0.008	0.008
37.50	37.50	212675	O54Pa	0.00	2.940	2.940
43.50	43.50	212680	m	0.00	<0.005	0.001
64.50	64.50	212695	O50Pb	0.00	0.848	0.848
70.50	70.50	212700	m	0.00	<0.005	0.001
92.00	92.00	212715	O61d	0.00	4.950	4.830
100.00	100.00	212720	m	0.00	<0.005	0.001
128.00	128.00	212735	O6Pc	0.00	1.560	1.560
135.00	135.00	212740	m	0.00	0.009	0.009
156.00	156.00	212755	O50Pb	0.00	0.832	0.832
162.00	162.00	212760	m	0.00	0.007	0.007
183.00	183.00	212775	O61d	0.00	4.870	4.930
189.00	189.00	212780	m	0.00	0.006	0.006
211.50	211.50	212795	O6Pc	0.00	1.615	1.615
217.50	217.50	212800	m	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-93

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : MJ Comeau

Du : 2009-11-22

Date de description : 2009-11-28

Au : 2009-11-25

Collet

UTM

Azimut : 171.36°

Plongée : -43.90°

Longueur : 208.50 m

Est 630 925.1

Nord 5 374 424.2

Élévation 312.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	4.00	170.00°	-45.00°	Non
Reflex	7.00	171.80°	-44.00°	Non
Reflex	10.00	172.00°	-44.20°	Non
Reflex	13.00	171.10°	-44.00°	Non
Reflex	16.00	172.80°	-44.00°	Non
Reflex	19.00	171.00°	-44.00°	Non
Reflex	22.00	172.40°	-43.90°	Non
Reflex	25.00	172.90°	-43.90°	Non
Reflex	28.00	172.00°	-43.90°	Non
Reflex	31.00	171.60°	-43.80°	Non
Reflex	34.00	173.30°	-43.70°	Non
Reflex	37.00	173.40°	-43.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	40.00	173.70°	-43.60°	Non
Reflex	43.00	173.00°	-43.50°	Non
Reflex	46.00	173.80°	-43.50°	Non
Reflex	49.00	174.00°	-43.60°	Non
Reflex	52.00	174.40°	-43.50°	Non
Reflex	55.00	173.90°	-43.50°	Non
Reflex	58.00	174.80°	-43.40°	Non
Reflex	61.00	174.40°	-43.40°	Non
Reflex	64.00	174.10°	-43.40°	Non
Reflex	67.00	174.70°	-43.50°	Non
Reflex	70.00	174.50°	-43.50°	Non
Reflex	73.00	175.40°	-43.40°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All down hole survey corrected for magnetic declination -12.5W.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	76.00	174.40°	-43.40°	Non	Reflex	175.00	178.90°	-43.00°	Non
Reflex	79.00	175.20°	-43.50°	Non	Reflex	178.00	178.80°	-42.90°	Non
Reflex	82.00	174.30°	-43.40°	Non	Reflex	181.00	179.00°	-43.00°	Non
Reflex	85.00	175.20°	-43.50°	Non	Reflex	184.00	178.20°	-42.80°	Non
Reflex	88.00	174.20°	-43.40°	Non	Reflex	187.00	179.10°	-42.90°	Non
Reflex	91.00	174.50°	-43.50°	Non	Reflex	190.00	177.60°	-42.80°	Non
Reflex	94.00	175.60°	-43.40°	Non	Reflex	193.00	177.90°	-42.90°	Non
Reflex	97.00	175.70°	-43.50°	Non	Reflex	196.00	178.20°	-42.90°	Non
Reflex	100.00	175.90°	-43.40°	Non	Reflex	199.00	179.70°	-42.80°	Non
Reflex	103.00	173.70°	-43.30°	Non	Reflex	202.00	178.60°	-42.90°	Non
Reflex	106.00	175.80°	-43.60°	Non	Reflex	205.00	178.10°	-42.60°	Non
Reflex	109.00	176.30°	-43.60°	Non	Reflex	208.00	178.20°	-42.60°	Non
Reflex	112.00	176.80°	-43.60°	Non					
Reflex	115.00	177.00°	-43.60°	Non					
Reflex	118.00	176.40°	-43.60°	Non					
Reflex	121.00	176.20°	-43.70°	Non					
Reflex	124.00	176.90°	-43.40°	Non					
Reflex	127.00	176.80°	-43.60°	Non					
Reflex	130.00	176.90°	-43.50°	Non					
Reflex	133.00	176.50°	-43.40°	Non					
Reflex	136.00	177.10°	-43.20°	Non					
Reflex	139.00	178.00°	-43.30°	Non					
Reflex	142.00	176.80°	-43.30°	Non					
Reflex	145.00	177.10°	-43.20°	Non					
Reflex	148.00	177.00°	-43.20°	Non					
Reflex	151.00	177.10°	-43.10°	Non					
Reflex	154.00	177.00°	-43.20°	Non					
Reflex	157.00	178.10°	-43.30°	Non					
Reflex	160.00	178.30°	-43.20°	Non					
Reflex	163.00	179.10°	-43.10°	Non					
Reflex	166.00	177.20°	-43.00°	Non					
Reflex	169.00	178.00°	-42.90°	Non					
Reflex	172.00	178.30°	-43.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.50	MT <b>Overburden</b>						
0.50	1.00	MT; I2D <b>Casing; Syenite</b> 0.5m recuperate from casing. All core 50cm of NW sent to lab for analysis sample # 211601						
0.50	25.50	limonite rich, broken up core, Py02 <b>Pyrite 02%</b> Dissiminated mm py from 1-2% From 9.2-9.5m: euhedral py up to 5mm. in qtz-car and in chl vns. 2%	0.50	1.00	211601	0.50	<0.005	0.001
1.00	21.45	SY; POR <b>Syenite; Porphyric</b> Syenite purple with chloritied zones, qtz-carb vlt x-cutting, diss py,  From 1-5.9m: MAG, chloritized porph ; 7% porph, mostly 5 to 10mm, up to 3cm, 3% vlt 45TCA From 5.9-11.20m: mostly purple syenite slightly chloritized. locally oxydized, 7% up to 5mm porph, 2% vlt From 11.20-21.45: Brecciated zones, syenitic angular clasts from 5mm up to 10cm, 7% porph from 5mm up to 30mm mostly cm porph.10% qtz-carbonate veins						
1.00	21.45	Chl <b>Chloritisation</b> locally chloritized, chloritized porph From 1-5.9m: 10% chl. Mag From 5.9-21.45m: 3% chloritization.	1.00	1.50	211602	0.50	0.005	0.005
			1.50	3.00	211603	1.50	<0.005	0.001
			3.00	4.50	211604	1.50	<0.005	0.001
			4.50	6.00	211605	1.50	0.006	0.006
			6.00	7.50	211606	1.50	0.089	0.089
			7.50	9.00	211607	1.50	0.008	0.008
			9.00	10.50	211608	1.50	0.028	0.028
			10.50	12.00	211609	1.50	0.015	0.015
			12.00	13.50	211610	1.50	0.188	0.188

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
21.45	40.00	<p>SY; MNZD</p> <p><b>Syenite; Mineralized</b></p> <p>syenite, qtz-carbonate vtls 1-3%</p> <p>From 21.45 to 23.9m: Syenite slithly mineralized. purple pinkish syenite with brecciated partially silicified mineralized zones. 7% 5mm porph.</p> <p>From 23.9 to 25.5m: mineralized syenite, brecciated, grey. 20% angular clasts from 5mm to 2cm. 7% mm porph</p> <p>From 25.5 to 30m: Foliated porphiric syenite. chloritized elongated porph, sericitic areas aleternating with purple pinkish syenite. traces of diss py. From 27.7- 27.85m strong pink "veins(?)" qtz-fds alternating with chlorite vns.</p> <p>From 30 to 33.5m: porph and locally brecciated locally foliated syenite. sericitic areas. 1% chl vtls, 20% angular to subangular clasts from 5mm to 5cm. 3% qtz-carbonate vtls.</p> <p>From 33.5- 34.5m: brecciated mineralized syenite, grey, sil, 20% very fine diss py, locally foliated, 10% subangular clasts from 5mm to 10cm, 20% of the clasts (or porph?)are replaced by sericite. locally oxydized</p>	13.50	15.00	211611	1.50	0.575		0.575
			15.00	16.50	211612	1.50	0.430		0.430
			16.50	18.00	211613	1.50	0.090		0.090
			18.00	19.50	211614	1.50	0.046		0.046
			19.50	21.00	211616	1.50	0.021		0.021
			21.00	22.50	211617	1.50	1.475		1.475
			22.50	24.00	211618	1.50	0.658		0.658
			24.00	25.50	211619	1.50	2.270		2.270
			21.45	25.50	<p>Sil; Chl</p> <p><b>Silicification; Chloritisation</b></p> <p>locally sil</p> <p>low chl</p>				
25.50	27.00	211620				1.50	0.630		0.630
27.00	28.50	211621				1.50	0.055		0.055
25.50	31.60	<p>Ser</p> <p><b>Sericitisation</b></p> <p>locally sericitized alternating with pinkish syenite.</p>	28.50	30.00	211622	1.50	0.047		0.047
25.50	30.00	<p>Py</p> <p><b>Pyrite</b></p> <p>Trace of diss mm py</p>							
30.00	33.50	<p>Py; Py07</p> <p><b>Pyrite ; Pyrite 07%</b></p>	30.00	31.50	211623	1.50	0.135		0.135
			31.50	33.00	211624	1.50	1.415		1.415

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		2% diss py up to 15% in grey sil veins							
31.60	40.00	Sil <b>Silicification</b> From 31.6 to 33.5m ps areas From 33.5 to 40m, ps to sil. grey. slightly sericitized	33.00	34.50	211625	1.50	4.090	4.07	4.070
33.50	40.00	Py10 <b>Pyrite 10%</b> from 5 to 20% very fine diss py oxydized areas	34.50	36.00	211626	1.50	1.600	5.42	1.600
			36.00	37.50	211627	1.50	5.030		5.420
			37.50	39.00	211628	1.50	1.230		1.230
			39.00	40.50	211629	1.50	0.715		0.715
40.00	52.50	SY; POR <b>Syenite; Porphyric</b> Porphyric syenite, 5% porph from 5mm to 3cm mostly chloritized. From 40-47.4m: redish syenite, 2% qtz-fds vns, 2% chlorite vlt. From 47.4-50.5m; redish and chloritized syenite, foliated with elongated chloritized clasts. 3%mm leucoxene. From 50.5- 50.8m : Massive silisification with chloritized elongated porph, we can find up to 5% of agglomerated py the porphyries. 3% CCp in qtz matrix. 2% of qtz veins. From 50.8-52.5m: FAULT zone at 50.8m, 12% of recuperation only	40.50	42.00	211630	1.50	0.547		0.547
			42.00	43.50	211631	1.50	0.135		0.135
			43.50	45.00	211632	1.50	0.088		0.088
			45.00	46.50	211633	1.50	0.036		0.036
			46.50	48.00	211634	1.50	0.117		0.117
40.00	50.50	Chl; Ser <b>Chloritisation; Sericitisation</b> From 40-47.4m: Chloritized porph in a redish syenite From 47.4-50.5m: Chloritized porph and sericitized matrix							
40.00	47.40	Py02 <b>Pyrite 02%</b> diss py							
47.40	50.50	Py01 <b>Pyrite 01%</b> Traces of fine diss py	48.00	49.50	211635	1.50	0.015		0.015
			49.50	51.00	211636	1.50	0.063		0.063
50.50	52.40	Sil; Chl <b>Silicification; Chloritisation</b> Strong sil syenite, from side to side of a fault at 50.8m Chloritized clasts in qtzic matrix							
50.50	50.80	Py; Cp							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
50.80	52.50	<p><b>Pyrite ; Chalcopyrite</b> up to 5% of agglomerated py the porphyries. 3% of agglomerated CCp in qtz matrix.</p> <p>FAI</p> <p><b>Fault</b> From 50.8-52.5m: FAULT zone at 50.8m, 12% of recuperation only</p>							
50.80	52.50	<p>Py01</p> <p><b>Pyrite 01%</b> 1-2% of diss py and agglomerated</p>	51.00	52.50	211637	1.50	0.202		0.202
52.40	86.20	<p>Chl; Alb; Ser</p> <p><b>Chloritisation; Albitisation; Sericitisation</b> Chloritized and albitized porph albite associated with qtz-carb vns. from 69.5-86.2m- 3% chlorite vns 3% of chloritized and epidotized segments with sericite locally</p>							
52.50	86.20	<p>SY; POR</p> <p><b>Syenite; Porphyric</b> Redish porphyric syenite porph : 7%, mostly from 1-2 cm, chloritized and albitized. Veins: qtz-carb vns and vlts, 2%. Chlorite vlts 1-2%</p>	52.50	54.00	211638	1.50	2.940		2.940
			54.00	55.50	211639	1.50	0.041		0.041
			55.50	57.00	211641	1.50	0.008		0.008
			57.00	58.50	211643	1.50	0.037		0.037
			58.50	60.00	211644	1.50	0.035		0.035
			60.00	61.50	211645	1.50	0.018		0.018
			61.50	63.00	211646	1.50	0.009		0.009
			63.00	64.50	211647	1.50	0.006		0.006
			64.50	66.00	211648	1.50	0.015		0.015
			66.00	67.50	211649	1.50	0.119		0.119
			67.50	69.00	211651	1.50	0.089		0.089
			69.00	70.50	211652	1.50	0.022		0.022
52.50	69.50	<p>Py02</p> <p><b>Pyrite 02%</b> 2% of diss py in matrix and in qtz vns very locally up to 5% of diss py</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
69.50	87.50	Py; Py02 <b>Pyrite ; Pyrite 02%</b> 2% of diss py, locally associated with dark chlorite vns (small amount of magnetite?) up to 5% locally	70.50	72.00	211653	1.50	0.016		0.016
			72.00	73.50	211654	1.50	0.194		0.194
			73.50	75.00	211655	1.50	<0.005		0.001
			75.00	76.50	211656	1.50	<0.005		0.001
			76.50	78.00	211657	1.50	<0.005		0.001
			78.00	79.50	211658	1.50	<0.005		0.001
			79.50	81.00	211659	1.50	<0.005		0.001
			81.00	82.50	211661	1.50	<0.005		0.001
			82.50	84.00	211662	1.50	<0.005		0.001
			84.00	85.50	211663	1.50	<0.005		0.001
		85.50	87.00	211664	1.50	0.014		0.014	
86.20	87.70	SY; FOL <b>Syenite; Foliation</b> the contact is oxydized foliated, epidotized sericitized syenite. elongated chloritized porph, chlorite vns diss py qtz-carb veins 1%							
86.20	87.70	Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> epidotized matrix with sericite. chloritized porph, and chl vns.	87.00	88.50	211665	1.50	0.247		0.247
87.50	87.60	Py; Py05 <b>Pyrite ; Pyrite 05%</b> 5% ammalgated py							
87.60	111.80	Py02 <b>Pyrite 02%</b> from 1-2% of diss py at 91,5m 3cm of broken up core oxydized with fresh 3%py							
87.70	111.80	SY; POR <b>Syenite; Porphyric</b> redish syenite with up to 7% of porph porph are chloritized and albitized. chloritized and epidotized corridors x-cutting the syenite 2% chlorite vls sometimes with magnetite. qtz-carb veins 2%, 30-40TCA							
87.70	111.80	Chl; Alb <b>Chloritisation; Albitisation</b>	88.50	90.00	211666	1.50	0.053		0.053

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Redish porphyric syenite chloritized and albitized porph Chlorite vlt 1-2% sericite in local foliated segments, 1-2%	90.00	91.50	211667	1.50	0.117		0.117
			91.50	93.00	211668	1.50	0.039		0.039
92.60	93.10	I2D; BR <b>Syenite; Brecciated</b> Brecciated syenite, just before this sub unit we can see amore condensed chl-mag vlt(3-4%) 3% of qtz-carb vns around clasts. clasts: angular from 5-10mm	93.00	94.50	211669	1.50	0.013		0.013
			94.50	96.00	211670	1.50	<0.005		0.001
			96.00	97.50	211671	1.50	0.071		0.071
			97.50	99.00	211672	1.50	0.032		0.032
			99.00	100.50	211673	1.50	0.199		0.199
			100.50	102.00	211674	1.50	0.258		0.258
			102.00	103.50	211675	1.50	0.092		0.092
			103.50	105.00	211676	1.50	0.008		0.008
			105.00	106.50	211677	1.50	0.010		0.010
			106.50	108.00	211678	1.50	0.137		0.137
			108.00	109.50	211679	1.50	0.236		0.236
			109.50	111.00	211681	1.50	0.011		0.011
			111.00	112.50	211682	1.50	0.146		0.146
111.80	117.80	SY; FOL <b>Syenite; Foliation</b> gradual contact with epidotized syenite, chloritized vns and mm elongated porph(3% porph) sericite associated with foliation qtz vns up to 1.5cm wide local oxydation							
111.80	117.80	Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> epidotized syenite sericite associated with foliation chloritized vns and mm elongated porph(3% porph) qtz vns up to 1.5cm wide							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
111.80	117.80	Py01 <b>Pyrite 01%</b> traces of diss py local oxydation with altered py in fractures mostrly from 116.4 up to 116.9m.	112.50	114.00	211683	1.50	0.115		0.115
			114.00	115.50	211684	1.50	0.071		0.071
			115.50	117.00	211685	1.50	0.012		0.012
			117.00	118.50	211686	1.50	<0.005		0.001
117.80	131.50	SY; MNZD <b>Syenite; Mineralized</b> Sharp contact with fault gouge at 117.8m for 3cm and oxydation. 2%qtz-carb vlts From 117.8-118.5m :epidotized and chloritised with oxydation in fractures, ps, From 118.5-120.5m: redish with epidotized-chl syenite, silicified, Qtz-fds veins. From 120.5-121.5m: grey sil, locally oxy, from 5-15% very fine diss py, qtz-fds veins From 121.5-126.8m: redish porphyric syenite (upper and lower contact are sharp foliated) From 126.8-131.5: contact strongly foliated ,sil syenite, chloritized-epidotized segments, mineralized							
117.80	117.90	T1C <b>Fault Gouge</b> 3cm of fault gouge at contact, with sil roundish clasts floating in the gouge							
117.80	118.50	Epi; Chl <b>Epidotisation; Chloritisation</b> From 117.8-118.5m :epidotized and chloritised with oxydation in fractures, ps,							
117.80	120.50	Py02 <b>Pyrite 02%</b> traces of diss py up to 2% of ammalgamated py							
118.50	120.50	Sil; Epi <b>Silicification; Epidotisation</b> redish with epidotized-chl syenite, silicified, Qtz-fds veins.	118.50	120.00	211687	1.50	0.081		0.081
			120.00	121.50	211688	1.50	1.580		1.580
120.50	121.50	Sil <b>Silicification</b> grey strong sil, locally oxy							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
120.50	121.50	Py10 <b>Pyrite 10%</b> from 5-15% nvery fine diss py, in strong sil matrix						
121.50	126.80	I2D; POR <b>Syenite; Porphyric</b> redish syenite with 7% porph of around 1cm.						
121.50	126.80	Epi <b>Epidotisation</b> redish porphyric syenite albitisation on porph, slithly epidotized porph						
121.50	126.80	Py; Py02 <b>Pyrite ; Pyrite 02%</b> 1-2% of diss py	121.50	123.00	211689	1.50	0.161	0.161
			123.00	124.50	211690	1.50	0.097	0.097
			124.50	126.00	211691	1.50	0.063	0.063
			126.00	127.50	211692	1.50	0.152	0.152
126.80	131.50	Sil <b>Silicification</b> ps to sil syenite. grey purple. chl-epidotized segments.						
126.80	131.50	Py; Py10 <b>Pyrite ; Pyrite 10%</b> From 5-15% of fine diss py	127.50	129.00	211693	1.50	0.036	0.036
			129.00	130.50	211694	1.50	0.871	0.871
			130.50	132.00	211695	1.50	2.190	2.190
131.50	141.00	AN <b>Trachyte</b> Trachytic dyke, sharp sil contact with syenite 20% of 2-3cm fds porph. 2% of epidotization						
131.50	141.00	Epi <b>Epidotisation</b> 2% of epidotiation	132.00	133.50	211697	1.50	0.080	0.080
			133.50	135.00	211698	1.50	<0.005	0.001
			135.00	136.50	211699	1.50	<0.005	0.001
			136.50	138.00	211701	1.50	0.006	0.006
			138.00	139.50	211702	1.50	0.155	0.155
			139.50	141.00	211703	1.50	0.120	0.120
141.00	170.50	SY; MNZD <b>Syenite; Mineralized</b> Syenite mineralized ( diss py and py vns) 3-5% porph, chl porh	141.00	142.50	211704	1.50	2.280	2.280
			142.50	144.00	211705	1.50	0.689	0.689
			144.00	145.50	211706	1.50	0.417	0.417

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		chl vlt(2%), qtz, qtz-carb vns(3-5%) x-cutting. redish to green (epidotized) to grey (silicified) syenite. !% of chlorite veins up to 1cm wide slightly brecciated from 153.3-155.7m, sil with angular clasts(7-15%) of syenite, qtz-carb vns	145.50	147.00	211707	1.50	0.008		0.008
141.00	145.80	Sil; Chl <b>Silicification; Chloritisation</b> ps to sil redish-grey syenite. chlorite alteration segments x-cutting the syenite							
141.00	145.80	Py; Py12 <b>Pyrite ; Pyrite 12%</b> 10-15% diss very fine py 2% of py in "veins"							
145.80	149.20	Epi; Chl; Sil <b>Epidotisation; Chloritisation; Silicification</b> Epidotized with chlorite segments x-cutting, local partial silicification							
145.80	149.20	Py; Py02 <b>Pyrite ; Pyrite 02%</b> diss py 1-2%	147.00	148.50	211708	1.50	0.604		0.604
			148.50	150.00	211709	1.50	1.185		1.185
149.20	170.50	Sil; Chl <b>Silicification; Chloritisation</b> Sil with chl alt. low epidotisaion	150.00	151.50	211710	1.50	1.130		1.130
			151.50	153.00	211711	1.50	0.084		0.084
			153.00	154.50	211712	1.50	3.690	4.02	4.020
			154.50	156.00	211713	1.50	1.435		1.435
			156.00	157.50	211714	1.50	1.125		1.125
149.20	157.00	Py15 <b>Pyrite 15%</b> very fine diss py and agglomerated from 10-20% at 153.9m 25% diss and agglomerated py							
157.00	163.00	Py; Py02 <b>Pyrite ; Pyrite 02%</b> 2% of diss py	157.50	159.00	211715	1.50	0.244		0.244
			159.00	160.50	211716	1.50	0.020		0.020
			160.50	162.00	211717	1.50	0.165		0.165
			162.00	163.50	211718	1.50	5.000	5.61	5.610

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
163.00	170.50	Py; Py15 <b>Pyrite ; Pyrite 15%</b> From 10-20% of diss very fine py	163.50	165.00	211719	1.50	1.825		1.825
			165.00	166.50	211721	1.50	1.850		1.850
			166.50	168.00	211722	1.50	0.423		0.423
			168.00	169.50	211723	1.50	2.530		2.530
			169.50	171.00	211724	1.50	1.230		1.230
170.50	208.50	SY; POR <b>Syenite; Porphyric</b> redish locally porphyric qtz-carb vns x-cutting the syenite 1-2%, from 5-10mm. chlorite vns 50TCA Qtz veins: 2%, albitized, up to 1cm thick x-cutting the syenite 40TCA From 170.5-194m: up to 5% porph 1cm; chloritized and albitized porph From 179.2-181.7: breccia, upper and lower contact are foliated with sericite-epidote-chlorite, clasts are angular up to 15cm mostly 3cm of syenite composition. qtz-carb matrix silicified. 2% diss py. From 194-208.5: up to 7% porph, 1cm , chlortized and albitized.							
170.50	208.50	Chl; Alb <b>Chloritisation; Albitisation</b> chloritized and albitized porph chlorite vns1-2% 50TCA albitized qtz veins. From 179.2-181.7m: ps to sil areas in this brecciated interval with albitization in earthy texture.							
170.50	208.50	Py02 <b>Pyrite 02%</b> diss and ammalgamated py 2% up to 10% of very fine diss py in some chloritized areas (1%)	171.00	172.50	211725	1.50	0.085		0.085
			172.50	174.00	211726	1.50	0.063		0.063
			174.00	175.50	211727	1.50	0.043		0.043
			175.50	177.00	211728	1.50	0.136		0.136
			177.00	178.50	211729	1.50	0.017		0.017
179.20	181.70	I2D; BR <b>Syenite; Brecciated</b> breccia, upper and lower contact are foliated with sericite-epidote-chlorite, clasts are angular up to 15cm mostly 3cm of syenite composition. qtz-carb matrix silicified. 2% diss	178.50	180.00	211730	1.50	0.033		0.033
			180.00	181.50	211731	1.50	0.013		0.013
			181.50	183.00	211732	1.50	0.128		0.128
			183.00	184.50	211733	1.50	0.122		0.122
			184.50	186.00	211734	1.50	0.070		0.070

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
py.	186.00	187.50	211735	1.50	0.219		0.219
	187.50	189.00	211736	1.50	0.051		0.051
	189.00	190.50	211737	1.50	<0.005		0.001
	190.50	192.00	211738	1.50	0.081		0.081
	192.00	193.50	211739	1.50	0.033		0.033
	193.50	195.00	211741	1.50	0.099		0.099
	195.00	196.50	211742	1.50	0.026		0.026
	196.50	198.00	211743	1.50	0.005		0.005
	198.00	199.50	211744	1.50	0.060		0.060
	199.50	201.00	211745	1.50	0.007		0.007
	201.00	202.50	211746	1.50	0.006		0.006
	202.50	204.00	211747	1.50	0.017		0.017
	204.00	205.50	211748	1.50	0.023		0.023
	205.50	207.00	211749	1.50	0.033		0.033
207.00	208.50	211751	1.50	<0.005		0.001	
208.50	Fin du sondage Nombre d'échantillons : 140 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 208.00						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
18.00	19.50	211615	O54Pa	1.50	2.950	2.950
54.00	55.50	211640	O61d	1.50	4.960	4.980
66.00	67.50	211650	m	1.50	<0.005	0.001
79.50	81.00	211660	O6Pc	1.50	1.600	1.600
108.00	109.50	211680	O61d	1.50	4.840	4.910
130.50	132.00	211696	O61d	1.50	4.780	4.990
135.00	136.50	211700	m	1.50	<0.005	0.001
163.50	165.00	211720	O54Pa	1.50	3.070	3.000
192.00	193.50	211740	O50Pb	1.50	0.866	0.866
205.50	207.00	211750	m	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-94

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C.Corriveau

Du : 2009-11-19

Date de description : 2009-11-29

Au : 2009-11-22

Collet

UTM

Azimut : 172.05°

Plongée : -54.60°

Longueur : 206.70 m

Est 630 916.9

Nord 5 374 448.3

Élévation 308.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	12.00	174.40°	-54.80°	Non
Reflex	15.00	175.30°	-54.80°	Non
Reflex	18.00	174.40°	-54.80°	Non
Reflex	21.00	173.20°	-54.70°	Non
Reflex	24.00	175.10°	-54.80°	Non
Reflex	27.00	175.80°	-54.90°	Non
Reflex	30.00	174.90°	-54.90°	Non
Reflex	33.00	175.40°	-54.90°	Non
Reflex	36.00	176.10°	-55.00°	Non
Reflex	39.00	176.20°	-54.90°	Non
Reflex	42.00	177.80°	-55.00°	Non
Reflex	45.00	177.10°	-54.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	48.00	177.20°	-54.90°	Non
Reflex	51.00	177.00°	-54.80°	Non
Reflex	54.00	177.20°	-54.70°	Non
Reflex	57.00	178.30°	-54.90°	Non
Reflex	60.00	178.50°	-54.90°	Non
Reflex	63.00	178.60°	-54.90°	Non
Reflex	66.00	177.70°	-54.80°	Non
Reflex	69.00	178.00°	-54.90°	Non
Reflex	72.00	179.00°	-55.00°	Non
Reflex	75.00	179.30°	-55.00°	Non
Reflex	78.00	179.30°	-55.10°	Non
Reflex	81.00	180.00°	-55.10°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All downhole survey corrected for mag declinaison -12.5W

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	84.00	180.20°	-55.20°	Non	Reflex	183.00	183.30°	-53.70°	Non
Reflex	87.00	180.00°	-55.30°	Non	Reflex	186.00	184.00°	-53.80°	Non
Reflex	90.00	180.70°	-55.20°	Non	Reflex	189.00	184.30°	-53.60°	Non
Reflex	93.00	180.70°	-55.20°	Non	Reflex	192.00	184.90°	-53.70°	Non
Reflex	96.00	179.50°	-55.10°	Non	Reflex	195.00	184.00°	-53.70°	Non
Reflex	99.00	179.40°	-55.20°	Non	Reflex	198.00	185.10°	-53.60°	Non
Reflex	102.00	180.50°	-55.30°	Non	Reflex	201.00	184.50°	-53.50°	Non
Reflex	105.00	181.10°	-55.40°	Non	Reflex	204.00	183.80°	-53.40°	Non
Reflex	108.00	180.00°	-55.30°	Non					
Reflex	111.00	180.10°	-55.40°	Non					
Reflex	114.00	180.70°	-55.40°	Non					
Reflex	117.00	180.50°	-55.30°	Non					
Reflex	120.00	180.70°	-55.30°	Non					
Reflex	123.00	180.80°	-55.00°	Non					
Reflex	126.00	182.10°	-54.70°	Non					
Reflex	129.00	182.00°	-54.50°	Non					
Reflex	132.00	181.50°	-54.30°	Non					
Reflex	135.00	181.60°	-54.20°	Non					
Reflex	138.00	181.40°	-54.10°	Non					
Reflex	141.00	181.30°	-54.00°	Non					
Reflex	144.00	182.30°	-54.10°	Non					
Reflex	147.00	182.80°	-53.90°	Non					
Reflex	150.00	182.30°	-53.80°	Non					
Reflex	153.00	182.60°	-53.90°	Non					
Reflex	156.00	183.10°	-53.80°	Non					
Reflex	159.00	181.80°	-53.80°	Non					
Reflex	162.00	183.50°	-53.90°	Non					
Reflex	165.00	183.30°	-53.90°	Non					
Reflex	168.00	182.50°	-53.80°	Non					
Reflex	171.00	183.40°	-53.80°	Non					
Reflex	174.00	184.20°	-53.90°	Non					
Reflex	177.00	183.90°	-53.90°	Non					
Reflex	180.00	184.70°	-53.80°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.30	MT <b>Overburden</b>						
3.30	3.80	MT; I2D; POR <b>Casing; Syenite; Porphyric</b> 50cm of HQ core recuperate from casing. All core sent to lab sample 226001 Redish to green porphyritic syenite. Idem litho next interval						
3.30	41.30	Ser; Chl; Oxy <b>Sericitisation; Chloritisation; Oxydation</b> Slightly sericitized and chloritized patch and segment giving green color.  14.5m-16.5m Strongly apple green sericitized and partially silicified segment.						
3.30	45.40	1% rusty oxydized fractures 55 TCA Py01 <b>Pyrite 01%</b> 1% disseminated fine grain Py	3.30	3.80	226001	0.50	0.019	0.019
3.80	41.30	SY; POR <b>Syenite; Porphyric</b> Redish to greenish syenite. Porphyritic texture. 3% thin carbonates spider web texture veinlets. 3% Grey silica-Qz-carbonates veins 2mm to cm. 1% black dark green chlorite veinlets.  Locally Mag (usually when not pervasively altered Sericite-Chl)  14.5m-16.4m Rusty upper contact. Strongly sericitized segment. Slightly foliated Chl-Sericite porphyries 25-30 TCA. 3% Py 2-3mm clusters  32.2m-32.5m Brecciated segment. Silica and qz-carb (minor chlorite) veins network. 2% Py and Hm	3.80	4.50	226002	0.70	0.027	0.027
			4.50	6.00	226003	1.50	0.176	0.176
			6.00	7.50	226004	1.50	0.054	0.054
			7.50	9.00	226005	1.50	0.014	0.014
			9.00	10.50	226006	1.50	0.010	0.010
			10.50	12.00	226007	1.50	0.024	0.024
			12.00	13.50	226008	1.50	0.057	0.057
			13.50	15.00	226009	1.50	0.309	0.309
			15.00	16.50	226011	1.50	0.255	0.255
			16.50	18.00	226012	1.50	0.032	0.032
			18.00	19.50	226013	1.50	0.023	0.023
			19.50	21.00	226014	1.50	0.073	0.073
			21.00	22.50	226015	1.50	0.077	0.077
			22.50	24.00	226016	1.50	0.417	0.417
			24.00	25.50	226017	1.50	0.091	0.091

Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
41.30	45.40	SY; FOL <b>Syenite; Foliation</b> Transition zone, probably minor fault zone. Green Aphanitic with porphyritic segments showing deformed porphyries following foliation. Strongly sericitized. Well foliated and fractured. Oxydized rusty fractures. Foliation 30 to 45 degrees TCA	25.50	27.00	226018	1.50	0.012		0.012		
			27.00	28.50	226019	1.50	<0.005		0.001		
			28.50	30.00	226020	1.50	<0.005		0.001		
			30.00	31.50	226021	1.50	0.006		0.006		
			31.50	33.00	226022	1.50	0.009		0.009		
			33.00	34.50	226023	1.50	0.013		0.013		
			34.50	36.00	226024	1.50	0.018		0.018		
			36.00	37.50	226025	1.50	0.189		0.189		
			37.50	39.00	226026	1.50	0.165		0.165		
			39.00	40.50	226027	1.50	<0.005		0.001		
		40.50	42.00	226028	1.50	<0.005		0.001			
41.30	45.40	Ser; Oxy <b>Sericitisation; Oxydation</b> Apple green foliated strongly sericitized segments. Rusty fractures parallel to foliation	42.00	43.50	226029	1.50	0.343		0.343		
			43.50	45.00	226031	1.50	0.006		0.006		
			45.00	46.50	226032	1.50	<0.005		0.001		
45.40	59.40	SY; POR <b>Syenite; Porphyric</b> Redish mottled syenite. Not mag. 5% white grey Qz-carb veins. Locally trace disseminated, coarse Py									
			45.40	59.40	Chl <b>Chloritisation</b> Weak chlorite altered porphyries.						
			45.40	59.40	Py; Hm <b>Pyrite ; Hematite</b> Traces disseminated Py	46.50	48.00	226033	1.50	0.006	0.006
						48.00	49.50	226034	1.50	0.005	0.005
						49.50	51.00	226035	1.50	<0.005	0.001
						51.00	52.50	226036	1.50	0.069	0.069
						52.50	54.00	226037	1.50	0.014	0.014
						54.00	55.50	226038	1.50	0.062	0.062

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
59.40	68.15	SY; MNZD <b>Syenite; Mineralized</b> Sharp upper contact 25 degree TCA. Partially to massively silicified grey to redish mineralized syenite. Locally brecciated. Py disseminated and stringers 5 to 10%  Brecciated Si-Carb lower contact over 30 cm. Alteration (Si) contact at 35-40 degreesTCA	55.50	57.00	226039	1.50	0.005	3.75	0.005
			57.00	58.50	226041	1.50	0.021		0.021
			58.50	60.00	226042	1.50	0.504		0.504
59.40	68.15	Sil <b>Silicification</b> Partially to strongly silicified discoloring rock to grey.. Si brecciating locally.							
59.40	68.15	Py <b>Pyrite</b> 5 to 10 % disseminated in matrix fine grain Py	60.00	61.50	226043	1.50	1.650	3.75	1.650
			61.50	63.00	226044	1.50	0.599		0.599
			63.00	64.50	226045	1.50	1.475		1.475
			64.50	66.00	226046	1.50	1.665		1.665
			66.00	67.50	226047	1.50	3.840		3.750
67.50	69.00	226048	1.50	0.767	0.767				
68.15	88.75	SY <b>Syenite</b> Redish greenish greyish porphyritic syenite. Short mineralized and partially silicified segments Py up to 3% (ex: 75.3m-76.65m)  3% white Qz-carb (+-albite) veins and breccia veins Py 1-2%  5-10% white carbonates veinlets spider web texture  2% disseminated fine grain leucoxene							
68.15	88.75	Ser <b>Sericitisation</b> Week to moderate sericitized segments. 5-10% green sericite veinlets and white carbonates veinlets.  5% chloritized feldspard porphyries.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
68.15	88.75	Partially silicified segment discolorating and bleaching host syenite. Py <b>Pyrite</b> Py up to 3% in Qz-Carb veins and silicified patches. Fine grain.	69.00	70.50	226049	1.50	0.207		0.207
			70.50	72.00	226051	1.50	0.280		0.280
			72.00	73.50	226052	1.50	0.468		0.468
			73.50	75.00	226053	1.50	0.484		0.484
			75.00	76.50	226054	1.50	1.355		1.355
			76.50	78.00	226055	1.50	0.646		0.646
			78.00	79.50	226056	1.50	0.096		0.096
			79.50	81.00	226057	1.50	0.064		0.064
			81.00	82.50	226058	1.50	0.130		0.130
			82.50	84.00	226059	1.50	0.167		0.167
			84.00	85.50	226060	1.50	0.008		0.008
			85.50	87.00	226061	1.50	0.133		0.133
			87.00	88.50	226062	1.50	0.195		0.195
			88.50	90.00	226063	1.50	1.150		1.150
88.75	106.70	SY; POR; FOL <b>Syenite; Porphyric; Foliation</b> Gradual upper contact oevr 1.2m. Partially silicified and mineralized discolorate to grey alteration. Qz-Si-Carb veins.  Green foliated syenite. Strongly sericitized and chloritized. Elongate chloritized porphyries following schistosity. 5% Si veins all directions.  Patchy grey partially silicified and mineralized segments and veins up to 5% Py  Strongly foliated and altered (chl-ser) lower contact over 2.15m							
88.75	106.70	Ser; Chl <b>Sericitisation; Chloritisation</b> Strong pervasive green sericitisation and chloritisation							
88.75	106.70	Py <b>Pyrite</b> Dicontinuous patchy grey partially silicified and mineralized segments and veins up to 5% Py	90.00	91.50	226064	1.50	0.622		0.622
			91.50	93.00	226065	1.50	0.164		0.164
			93.00	94.50	226066	1.50	0.218		0.218

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
106.70	122.40	BX; I2D; MNZD <b>Breccia; Syenite; Mineralized</b> Medium grey to dark grey silicified mineralized hydrolic breccia. Matrix supported with minor segments clasts supported. 2mm to 4cm subangular clasts. Clast of very altered intrusive syenite (few qz porphyries in clasts still visibles). Matrix is essentially silica-carbonates and pyrite. Clasts are often crack and/or mineralized with fine Py.  Green sericitic patches patially silicified.  5% thin qz-carbonates spider web texture veinlets.  Not mag  Mineralized Py and AsPy  Lower contact: White to grey 60cm Qz vein 35 TCA 2% Py stringers and disseminated. 5-10% greenish sericite veinlets	94.50	96.00	226067	1.50	0.304		0.304
			96.00	97.50	226068	1.50	0.714		0.714
			97.50	99.00	226069	1.50	0.519		0.519
			99.00	100.50	226071	1.50	0.416		0.416
			100.50	102.00	226072	1.50	0.249		0.249
			102.00	103.50	226073	1.50	0.141		0.141
			103.50	105.00	226074	1.50	0.395		0.395
			105.00	106.50	226075	1.50	0.184		0.184
			106.50	108.00	226076	1.50	2.360		2.360
106.70	122.40	Sil; Ser <b>Silicification; Sericitisation</b> Partial to massive silicification discoloring host rock to grey. 10% Greenish patches and veins/veinlets sericitized							
106.70	122.40	Py; As; Hm <b>Pyrite ; Arsenopyrite ; Hematite</b> 5 to 20 % fine grain Py in matrix and in clasts. 2-4% locally Py stringers. 3% Aspy disseminated (ex: 116.6m - 117m)	108.00	109.50	226077	1.50	0.515	3.87	0.515
			109.50	111.00	226078	1.50	0.996		0.996
			111.00	112.50	226079	1.50	2.810		2.810
			112.50	114.00	226081	1.50	3.610		3.870



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
122.40	146.80	<p>Rare blueish hematite clusters</p> <p>SY; MNZD; BR; POR</p> <p><b>Syenite; Mineralized; Brecciated; Porphyric</b></p> <p>Dark grey purple to greenish porphyritic mineralized syenite. 5-15 % Py disseminated, clusters and stringers..</p> <p>Grey color cause by silicification. Hydrothermal Si+Py alteration brecciating locally.</p> <p>3% Fine white carbonates spider web veinlets.</p> <p>Partial to massive silicification. 10% Qz-Si-Py +- carb breccia veins and veinlets. Small segments brecciated. Not Mag.</p> <p>Gradual foliated sericitized interlayered with Qz-carb cm veins gradual lower contact over 20cm</p>	114.00	115.50	226082	1.50	1.940		1.940
			115.50	117.00	226083	1.50	5.600	5.62	5.620
			117.00	118.50	226084	1.50	4.990	4.98	4.980
			118.50	120.00	226085	1.50	3.970	3.92	3.920
			120.00	121.50	226086	1.50	1.675		1.675
			121.50	123.00	226087	1.50	4.970	4.82	4.820
			122.40	146.80	<p>Sil; Alb</p> <p><b>Silicification; Albitisation</b></p> <p>Strongly to massive pervasive silicification discoloring and locally brecciation the syenite.</p> <p>White earthy albite patch in Qz-Fp-Carb veins. Also whitish veinlets.</p>				
122.40	146.80	<p>Py</p> <p><b>Pyrite</b></p> <p>5 to 20% Very fine disseminated, clusters and stringers of fine Py</p>	123.00	124.50	226088	1.50	2.360		2.360
			124.50	126.00	226089	1.50	0.805		0.805
			126.00	127.50	226091	1.50	0.458		0.458
			127.50	129.00	226092	1.50	1.370		1.370
			129.00	130.50	226093	1.50	0.296		0.296
			130.50	132.00	226094	1.50	3.120	3.03	3.030
			132.00	133.50	226095	1.50	4.780	4.61	4.610
			133.50	135.00	226096	1.50	4.740	4.75	4.750
			135.00	136.50	226097	1.50	5.260	4.68	4.680
			136.50	138.00	226098	1.50	3.120	3.13	3.130
			138.00	139.50	226099	1.50	5.250	5.28	5.280
139.50	141.00	226100	1.50	4.120	4.04	4.040			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
146.80	172.50	<p>SY; APH; POR; MNZD</p> <p><b>Syenite; Aphanitic; Porphyric; Mineralized</b></p> <p>Grey redish to green mineralized with leached patch porphyritic syenite.</p> <p>Still mineralized but not consistant. Usually segment Py rich surrounded by leached aphanitic or mottled zones. Mineralization found in darker grey partially Si segments and veins.</p> <p>3% Qz-carb veins.</p> <p>2-4% blackish chlorite veins and brecciated veins.</p> <p>158.2-158.55m Qz-carb-Tourmaline veins. 3cm to 2mm wide.</p> <p>Shap chloritized lower contact</p>	141.00	142.50	226101	1.50	4.970	4.84	4.840
			142.50	144.00	226102	1.50	2.160		2.160
			144.00	145.50	226103	1.50	2.480		2.480
			145.50	147.00	226104	1.50	3.030		2.940
146.80	172.50	<p>Si; Ser; Alb</p> <p><b>Silicification; Sericitisation; Albitisation</b></p> <p>Partially silicified segments.</p> <p>White earthy albite patch in Qz-Fp-Carb veins. Also whitish albitized veinlets.</p> <p>Pervasive Sericite and veinlets</p>	147.00	148.50	226105	1.50	0.495	3.66	0.495
			148.50	150.00	226106	1.50	2.670		2.670
			150.00	151.50	226107	1.50	2.070		2.070
			151.50	153.00	226108	1.50	2.600		2.600
			153.00	154.50	226109	1.50	3.890		3.660
			154.50	156.00	226111	1.50	1.225		1.225
			156.00	157.50	226112	1.50	0.779		0.779
			157.50	159.00	226113	1.50	1.230		1.230
			159.00	160.50	226114	1.50	0.489		0.489
			160.50	162.00	226115	1.50	0.021		0.021
			162.00	163.50	226116	1.50	0.016		0.016
			163.50	165.00	226117	1.50	0.511		0.511

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
172.50	181.05	AN; POR <b>Trachyte; Porphyric</b> Sharp upper contact 172-172.3m White pinkish Qz-Fp-Carb veins  Redish to greenish with 40 % whitish feldspars porphyries trachytic dyke. Interlayered of grey aphanitic pyritized (up to 5-10%) and silicified segments (ex: 179.95 to 180.35m, 182.1-182.3m). Also mineralized (Py 2% diss) discolored to purple grey porphyritic segments. 3% white Qz-carb veins  3% white carbonates spider web texture veinlets. 8% green sericite chlorite pervasive and veinlets.	165.00	166.50	226118	1.50	1.720		1.720
			166.50	168.00	226119	1.50	2.230		2.230
			168.00	169.50	226120	1.50	0.248		0.248
			169.50	171.00	226121	1.50	0.931		0.931
			171.00	172.50	226122	1.50	0.164		0.164
172.50	181.05	Ser; Sil; Sil <b>Sericitisation; Silicification; Silicification</b> 8% green sericite chlorite veinlets and pervasive patchy apple green. Weak Si discolorating to tally to partially obliterating primary texture.							
172.50	181.05	Py; Hm <b>Pyrite ; Hematite</b> 5-10% fine Py in grey aphanitic silicified segments (ex: 179.95 to 180.35m, 182.1-182.3m). 2% disseminated and stringers of Py in discolored to purple grey porphyritic segments. Disseminated 1mm Hm clusters	172.50	174.00	226123	1.50	0.035		0.035
			174.00	175.50	226124	1.50	0.161		0.161
			175.50	177.00	226125	1.50	0.121		0.121
			177.00	178.50	226126	1.50	0.285		0.285
			178.50	180.00	226127	1.50	0.390		0.390
		180.00	181.50	226128	1.50	0.665		0.665	
181.05	195.50	SY; APH; TZ <b>Syenite; Aphanitic; Transition zone</b> Presume Syenite. Very altereared leached sericite chlorite obliterated almost totally the primary texture. 1% disseminated Py							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
181.05	195.50	Ser; Chl <b>Sericitisation; Chloritisation</b> Strong sericitization with moderate chloritisation						
181.05	195.50	Py <b>Pyrite</b> 2% disseminated Py	181.50	183.00	226129	1.50	0.140	0.140
			183.00	184.50	226131	1.50	0.016	0.016
			184.50	186.00	226132	1.50	0.008	0.008
			186.00	187.50	226133	1.50	0.009	0.009
			187.50	189.00	226134	1.50	0.012	0.012
			189.00	190.50	226135	1.50	0.007	0.007
			190.50	192.00	226136	1.50	0.015	0.015
			192.00	193.50	226137	1.50	0.011	0.011
			193.50	195.00	226138	1.50	0.006	0.006
			195.00	196.50	226139	1.50	0.043	0.043
195.50	206.70	SY; BR <b>Syenite; Brecciated</b> Fine grain dark purple, green to black very altered syenite. Mineralized segments and brecciated segments. Black tourmaline veins at 201.3m. 3% Qz-carb veins.  upper alteration contact 45TCA						
195.50	206.70	Sil; Ser <b>Silicification; Sericitisation</b> Partially silicified Sericite veinlets and pervasive segments very altered and bleached						
195.50	206.70	Py <b>Pyrite</b> Mineralized and brecciated pyritized segments 3% py disseminated and stringers.	196.50	198.00	226141	1.50	<0.005	0.001
			198.00	199.50	226142	1.50	<0.005	0.001
			199.50	201.00	226143	1.50	<0.005	0.001
			201.00	202.50	226144	1.50	1.380	1.380
			202.50	204.00	226145	1.50	0.559	0.559
			204.00	205.50	226146	1.50	0.021	0.021
			205.50	206.70	226147	1.20	0.009	0.009
206.70	<b>Fin du sondage</b> Nombre d'échantillons : 137 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 203.40							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.50	15.00	226010	O50Pb	1.50	0.873	0.873
42.00	43.50	226030	O50Pb	1.50	0.839	0.839
55.50	57.00	226040	m	1.50	<0.005	0.001
69.00	70.50	226050	O61d	1.50	4.830	4.890
97.50	99.00	226070	O54Pa	1.50	2.980	2.980
111.00	112.50	226080	m	1.50	0.005	0.005
124.50	126.00	226090	O61d	1.50	4.870	4.850
153.00	154.50	226110	O54Pa	1.50	3.010	2.980
181.50	183.00	226130	O6Pc	1.50	1.555	1.555
195.00	196.50	226140	m	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> B09-95	Titre minier : CM 292	Section :
	Canton : Duparquet	Niveau : surface
	Rang :	Place de travail : Beattie mine site
Foré par : Foramex	Lot :	
Décrit par : Maria Jose Comeau	Du : 2009-11-25	Date de description : 2009-12-01
	Au : 2009-11-27	

Collet

Azimut : 164.64°  
 Plongée : -44.70°  
 Longueur : 209.50 m

UTM

Est	630 946.8
Nord	5 374 432.4
Élévation	312.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	166.10°	-45.30°	Non
Reflex	11.00	168.30°	-45.30°	Oui
Reflex	14.00	167.30°	-45.30°	Non
Reflex	17.00	166.50°	-45.30°	Non
Reflex	20.00	166.10°	-45.30°	Non
Reflex	23.00	166.00°	-45.40°	Non
Reflex	26.00	166.30°	-45.40°	Non
Reflex	29.00	167.40°	-45.40°	Non
Reflex	32.00	166.50°	-45.40°	Non
Reflex	35.00	166.10°	-45.40°	Non
Reflex	38.00	166.30°	-45.40°	Non
Reflex	41.00	167.30°	-45.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	166.40°	-45.10°	Non
Reflex	47.00	167.70°	-45.20°	Non
Reflex	50.00	168.20°	-45.10°	Non
Reflex	53.00	167.80°	-44.90°	Non
Reflex	56.00	168.10°	-44.80°	Non
Reflex	59.00	168.60°	-44.70°	Non
Reflex	62.00	167.30°	-44.60°	Non
Reflex	65.00	167.90°	-44.60°	Non
Reflex	68.00	168.50°	-44.60°	Non
Reflex	71.00	168.00°	-44.60°	Non
Reflex	74.00	168.20°	-44.60°	Non
Reflex	77.00	167.80°	-44.60°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All down hole survey corrected for magnetic declination -12.5W.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	167.60°	-44.70°	Non	Reflex	179.00	171.30°	-44.30°	Non
Reflex	83.00	167.30°	-44.60°	Non	Reflex	182.00	170.60°	-44.20°	Non
Reflex	86.00	168.10°	-44.70°	Non	Reflex	185.00	170.00°	-44.10°	Non
Reflex	89.00	167.60°	-44.70°	Non	Reflex	188.00	170.80°	-44.20°	Non
Reflex	92.00	168.80°	-44.70°	Non	Reflex	191.00	170.20°	-44.10°	Non
Reflex	95.00	168.70°	-44.80°	Non	Reflex	194.00	171.70°	-44.10°	Non
Reflex	98.00	169.40°	-44.60°	Oui	Reflex	197.00	171.70°	-44.20°	Non
Reflex	101.00	167.90°	-44.70°	Non	Reflex	200.00	171.30°	-44.10°	Non
Reflex	104.00	167.90°	-44.60°	Non	Reflex	203.00	169.60°	-44.10°	Oui
Reflex	107.00	168.50°	-44.60°	Non	Reflex	206.00	171.80°	-44.00°	Non
Reflex	110.00	168.60°	-44.70°	Non	Reflex	209.00	171.00°	-44.00°	Non
Reflex	113.00	169.70°	-44.60°	Non					
Reflex	116.00	170.00°	-44.50°	Non					
Reflex	119.00	169.90°	-44.50°	Non					
Reflex	122.00	170.10°	-44.50°	Non					
Reflex	125.00	169.10°	-44.40°	Non					
Reflex	128.00	168.70°	-44.40°	Non					
Reflex	131.00	168.90°	-44.40°	Non					
Reflex	134.00	170.10°	-44.50°	Non					
Reflex	137.00	169.20°	-44.50°	Non					
Reflex	140.00	169.30°	-44.50°	Non					
Reflex	143.00	169.40°	-44.40°	Non					
Reflex	146.00	168.70°	-44.40°	Non					
Reflex	149.00	168.70°	-44.40°	Non					
Reflex	152.00	170.60°	-44.50°	Non					
Reflex	155.00	170.20°	-44.30°	Non					
Reflex	158.00	170.20°	-44.40°	Non					
Reflex	161.00	170.00°	-44.20°	Non					
Reflex	164.00	171.10°	-44.20°	Non					
Reflex	167.00	170.90°	-44.30°	Non					
Reflex	170.00	170.10°	-44.20°	Non					
Reflex	173.00	169.90°	-44.20°	Oui					
Reflex	176.00	171.30°	-44.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.80	MT <b>Overburden</b>						
0.80	1.50	MT; I2D <b>Casing; Syenite</b> purple syenite with up to 5% porph  recuperate from casing. All core 2.2m of NW sent to lab for analysis sample # 211752. broken up core,	0.80	1.50	211752	0.70	0.270	0.270
1.50	3.00	MT; I2D <b>Casing; Syenite</b> purple syenite with up to 5% porph  recuperate from casing. All core 2.2m of NW sent to lab for analysis sample # 211753. broken up core,	1.50	3.00	211753	1.50	0.074	0.074
3.00	16.40	SY <b>Syenite</b> purple syenite with up to 5% porph( from 5mm to 15mm, mostly 5mm) qtz-carb vns (2%) 2-7mm 40TCA. 1-2% chl vlts. oxydized in fractures. locally mag						
3.00	21.30	Chl; Alb <b>Chloritisation; Albitisation</b> redish purple syenite qtz-carb vlts. albitisation-chloritisation on porph, chl vlts. From 3-6.2m: Mag From 9.5-15.7: Mag	3.00	4.00	211754	1.00	0.005	0.005
			4.00	5.50	211755	1.50	0.005	0.005
			5.50	7.00	211756	1.50	0.006	0.006
			7.00	8.50	211757	1.50	0.111	0.111
			8.50	10.00	211758	1.50	0.006	0.006
			10.00	11.50	211759	1.50	0.036	0.036
			11.50	13.00	211760	1.50	0.006	0.006
			13.00	14.50	211761	1.50	0.005	0.005
14.50	20.00	Py01 <b>Pyrite 01%</b> traces of diss py	14.50	16.00	211762	1.50	0.006	0.006
			16.00	17.50	211763	1.50	0.005	0.005
16.40	21.30	SY; BR	17.50	19.00	211764	1.50	0.005	0.005



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<p><b>Syenite; Brecciated</b> purple syenite locally brecciated 3% chl porph mostly 5mm. clasts are of syenitic composition, from 5 to 50mm dark chlorite injected in between the clasts up to 20m then silica is injected between the clasts.</p>	19.00	20.50	211765	1.50	0.114		0.114
20.00	29.50	<p>Py05 <b>Pyrite 05%</b> very fine diss py from 2-15%</p>	20.50	22.00	211766	1.50	0.048		0.048
21.30	40.40	<p>SY; MNZD <b>Syenite; Mineralized</b> oxydized and broken up upper contact qtz-carb vns2%. qtz-fds vns 2%. From 21.3-27.1: silicified brecciated mineralized syenite. grey, angular clasts up to 15% from 5mm up to 150mm. mineralized.(in some sections we can see rounded fds porph) From 27.1-33.7: redish purple porph syenite, locally brecciated, porph locally oriented. porph up to 15% from 3mm up to 20mm (mostly 5mm), week mineralisation. From 33.7-36.2: brecciated syenite minerelized. redish purple to grey to light green. angular clasts from 1-30cm, sil matrix around clasts, mineralised, ending with an epidotized weekely foliated segment. From 36.2-37m: sharp contact. grey strong sil brecciated syenite, strong mineralisation, albitisation earthy texture, angular clasts 30% . 5% epidotized porph. From 37-40.4m: foliated epidotized-sericitized syenite. oxydized segments.</p>	22.00	23.50	211767	1.50	2.830		2.830
			23.50	25.00	211768	1.50	1.025		1.025
			25.00	26.50	211769	1.50	0.658		0.658
			26.50	28.00	211771	1.50	0.622		0.622
21.30	27.10	<p>Sil <b>Silicification</b> grey silicified brecciated syenite qtz-carb veins 2%.</p>							
27.10	33.70	<p>Chl <b>Chloritisation</b> redish purple syenite week chloritisation: on clasts (5% of porph are chloritized) and vns 2%.</p>	28.00	29.50	211772	1.50	0.465		0.465

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
29.50	36.20	Py02 <b>Pyrite 02%</b> diss py very fine, from 1-5%	29.50	31.00	211773	1.50	0.011		0.011
			31.00	32.50	211774	1.50	0.025		0.025
			32.50	34.00	211775	1.50	0.030		0.030
33.70	36.20	Epi; Alb; Chl <b>Epidotisation; Albitisation; Chloritisation</b> brecciated syenite redish purple with chl vlt and locally, chloritized porph local epidotisation in matrix qtz-carb-allb vns.	34.00	35.50	211776	1.50	0.150		0.150
			35.50	37.00	211777	1.50	0.675		0.675
36.20	37.00	Sil; Alb; Epi <b>Silicification; Albitisation; Epidotisation</b> grey brecciated silicified qtz-carb vns albitisation in earth texture local epidotisation							
36.20	37.00	Py15 <b>Pyrite 15%</b> up to 15% very fine diss py							
37.00	40.40	Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> foliated syenite epidote colour with chloritized elongated porph							
37.00	45.80	Py02 <b>Pyrite 02%</b> 1-2% of very fine diss py and agglomerated py in matrix and on elongated chloritized porph. oxydized segments	37.00	38.50	211778	1.50	0.130		0.130
			38.50	40.00	211779	1.50	0.068		0.068
			40.00	41.50	211780	1.50	0.819		0.819
40.40	45.80	SY <b>Syenite</b> redish with light green segments segments 5% fds porph, mostly 5mm, from 2-15mm. chl vlt 1%, qtz-carb vlt and surrounding clasts 1%. locally brecciated, 2% of angular clasts from 3mm-15mm, redish syenite composition.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
40.40	45.80	Epi; Chl <b>Epidotisation; Chloritisation</b> epidotized-chloritized segments chlorite vns. locally partially silicified	41.50	43.00	211781	1.50	1.385		1.385
			43.00	44.50	211782	1.50	0.370		0.370
			44.50	46.00	211783	1.50	0.719		0.719
45.80	50.60	BX; I2D; MNZD; BSF <b>Breccia; Syenite; Mineralized; Breccia Silicified zone</b> grey brecciated mineralized syenite locally foliated. from ps to silicified. angular clasts from 5mm up to 70mm, upper clasts are redish, getting grey when more sil, some are epidotized in the lower part. upper contact is foliated and brecciated, lower contact is foliated. mineralized, oxydized segments.							
45.80	50.60	Sil; Epi; Ser <b>Silicification; Epidotisation; Sericitisation</b> silicified matrix and clasts locally epidotized							
45.80	50.60	Py07 <b>Pyrite 07%</b> from 5-15% of very fine diss py rusty segments.	46.00	47.50	211784	1.50	0.770		0.770
			47.50	49.00	211785	1.50	1.635		1.635
			49.00	50.50	211786	1.50	2.920		2.920
			50.50	52.00	211787	1.50	0.065		0.065
50.60	58.90	SY; FOL <b>Syenite; Foliation</b> syenite, locally foliated, From 50.6-52.2: epidotized sericitized foliated syenite. elongated chloritized porph. chl vlt1%, qtz-carb vns and vlt2%. From 52.2-58.9: syenite, locally foliated, redish with greenish segments. chl vlt 2-3%, 30TCA. fds-qtz-carb vns 2-3%,35-40TCA. 25% of porph are elongated and chloritized, 75% are fds from 5mm-20mm, 5% porph.							
50.60	52.40	Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> pervasive epidotisation and sericitation. chloritized elongated porph, chl vlt,							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
50.60	93.40	Py02 <b>Pyrite 02%</b> 2% diss and amalgamated py, up to 5% in restraint areas.	52.00	53.50	211788	1.50	0.084		0.084
52.40	73.50	Chl <b>Chloritisation</b> chl veins up to 3%, from mm up to 1cm. chloritized porph.	53.50	55.00	211789	1.50	0.153		0.153
			55.00	56.50	211791	1.50	0.262		0.262
			56.50	58.00	211792	1.50	0.093		0.093
			58.00	59.50	211793	1.50	0.074		0.074
58.90	93.40	SY; POR <b>Syenite; Porphyric</b> redish syenite, 7% porph from 5-30mm, mostly 1cm. qtz-fds-carb veins up to 5% up to 2cm wide, pinkish to white. chlorite vns2% up to 1cm wide. locally brecciated with qtz-carb matrix around clasts (1% of brecciated segments). locally up to 5% py .	59.50	61.00	211794	1.50	0.016		0.016
			61.00	62.50	211795	1.50	0.032		0.032
			62.50	64.00	211796	1.50	0.008		0.008
			64.00	65.50	211797	1.50	0.037		0.037
			65.50	67.00	211798	1.50	0.014		0.014
			67.00	68.50	211799	1.50	0.019		0.019
			68.50	70.00	211801	1.50	0.014		0.014
			70.00	71.50	211802	1.50	0.008		0.008
			71.50	73.00	211803	1.50	0.006		0.006
			73.00	74.50	211804	1.50	0.017		0.017
73.50	77.90	Epi; Chl <b>Epidotisation; Chloritisation</b> pervasive epidotization and chloritisation., 5% chloritized porph	74.50	76.00	211805	1.50	0.016		0.016
			76.00	77.50	211806	1.50	0.054		0.054
			77.50	79.00	211807	1.50	0.056		0.056
77.90	93.40	Chl <b>Chloritisation</b> redish porph syenite chloritized rim around fds porph local epidotisation, local sericitation in mm segments. 2% qtz-carb vns	79.00	80.50	211808	1.50	0.011		0.011
			80.50	82.00	211809	1.50	0.017		0.017
			82.00	83.50	211811	1.50	0.008		0.008
			83.50	85.00	211812	1.50	0.007		0.007
			85.00	86.50	211813	1.50	0.006		0.006
			86.50	88.00	211814	1.50	0.023		0.023
			88.00	89.50	211815	1.50	0.061		0.061
			89.50	91.00	211816	1.50	0.018		0.018
			91.00	92.50	211817	1.50	0.035		0.035
			92.50	94.00	211818	1.50	0.338		0.338
93.40	94.00	SY; FOL <b>Syenite; Foliation</b> epidotized foliated syenite							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
93.40	94.00	elongated chloritized porph, 3% porph qtz-fds vns, qtz-carb vns mineralized Epi; Ser; Chl <b>Epidotisation; Sericitisation; Chloritisation</b> foliated segment pervasive epidotisation, elongated chloritized porph sericite in foliated matrix						
93.40	94.00	Py <b>Pyrite</b> very fine diss py, up to 5% in foliated epidotized syenite						
94.00	96.20	SY; POR <b>Syenite; Porphyric</b> purple grey porph syenite 5% porph, qtz-carb vns 3%.						
94.00	96.20	Epi; Chl <b>Epidotisation; Chloritisation</b> redish purple syenite local epidotized and chloritized porph						
94.00	96.20	Py01 <b>Pyrite 01%</b> diss py. 1 up to 2%.	94.00	95.50	211819	1.50	0.077	0.077
			95.50	97.00	211820	1.50	0.928	0.928
96.20	97.00	SY; MNZD <b>Syenite; Mineralized</b> grey to purple mineralized syenite from ps to silicified. qtz-fds veins 1%, qtz-carb veins 2%						
96.20	97.00	Sil; Epi <b>Silicification; Epidotisation</b> grey purple syenite silicified segment albitized porph and epidotized porph qtz-carb vns 1-2%						
96.20	97.00	Py07 <b>Pyrite 07%</b> from 5-10% of very fine diss py						

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
97.00	110.50	SY; POR <b>Syenite; Porphyric</b> redish porphiric syenite 5-7% porph, mostly 10mm: from 5mm up to 30mm. chloritized rim. qtz-carb vns-vlts 3%. 1% chl vlts. 1% qtz-fds vns						
97.00	110.50	Chl <b>Chloritisation</b> redish porph syenite chloritized porph. qtz-carb vns 1%	97.00	98.50	211821	1.50	0.084	0.084
			98.50	100.00	211822	1.50	0.111	0.111
			100.00	101.50	211823	1.50	0.013	0.013
			101.50	103.00	211824	1.50	0.009	0.009
			103.00	104.50	211825	1.50	0.006	0.006
			104.50	106.00	211826	1.50	0.006	0.006
			106.00	107.50	211827	1.50	0.007	0.007
			107.50	109.00	211828	1.50	0.026	0.026
97.00	108.80	Py02 <b>Pyrite 02%</b> diss and agglomerated py						
108.80	116.70	Py04 <b>Pyrite 04%</b> very fine to fine diss and ammalgameted py mostly 2%, up to 7% in very local areas. mostly in silicified oxydized fractures	109.00	110.50	211829	1.50	0.162	0.162
110.50	114.50	SY; FOL <b>Syenite; Foliation</b> light green foliated syenite upper contact is brecciated elongated chloritized porph, 5% porph 1-2cm long epidotized-sericitized matrix localy silicified with milky qtz veins intruding the foliated syenite 1-2% diss py up to 5% in limited areas.						
110.50	114.50	Ser; Epi; Chl; Sil <b>Sericitisation; Epidotisation; Chloritisation;</b> <b>Silicification</b>	110.50	112.00	211831	1.50	0.118	0.118
			112.00	113.50	211832	1.50	0.219	0.219
			113.50	115.00	211833	1.50	0.014	0.014

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
114.50	162.20	foliated syenite light green sericite and epidotized matrix, chloritized elongated porph locally white silica veins SY; POR <b>Syenite; Porphyric</b> redish porph syenite greenish segments entering the redish syenite porph: from 5-10%, chloritized porph, from 5to20mm porph mostly 1cm. 2% dark chloritized vlts 2-3% qtz-carb vns, mostly 40TCA locally foliated with sericite and epidote From 138.7-138.9: brecciated syenite: grey purple silicified clasts, matrix is milky qtz From 152.7-153.3: foliated syenite, porph still visible, sericite-epitode-chl alt	115.00	116.50	211834	1.50	0.009		0.009
			116.50	118.00	211835	1.50	<0.005		0.001
114.50	138.00	Chl; Ser <b>Chloritisation; Sericitisation</b> redish porph syenite chloritized porph and chl (very dark) veins. local sericitasion in foliated-brecciated segments. locally silicified in brecciated areas.							
116.70	122.00	Py05 <b>Pyrite 05%</b> 2% of ammalgamated py and disseminated up to 7% up to 5% of ammalgamated py in redish syenite	118.00	119.50	211836	1.50	0.005		0.005
			119.50	121.00	211837	1.50	0.030		0.030
			121.00	122.50	211838	1.50	0.038		0.038
122.00	150.50	Py02 <b>Pyrite 02%</b> diss and ammalgamted py	122.50	124.00	211839	1.50	0.064		0.064
			124.00	125.50	211840	1.50	1.095		1.095
			125.50	127.00	211841	1.50	0.420		0.420
			127.00	128.50	211842	1.50	0.028		0.028
			128.50	130.00	211843	1.50	0.050		0.050
			130.00	131.50	211844	1.50	0.430		0.430
			131.50	133.00	211845	1.50	0.007		0.007
			133.00	134.50	211846	1.50	0.005		0.005
			134.50	136.00	211848	1.50	0.009		0.009
			136.00	137.50	211849	1.50	0.116		0.116
			137.50	139.00	211851	1.50	0.357		0.357

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
138.00	140.00	Chl; Alb; Sil <b>Chloritisation; Albitisation; Silicification</b> redish porph syenite chloritized porph and chl (very dark) veins. local sericitasion in foliated-brecciated segments. locally silicified in brecciated areas. albitisation in spyderweb	139.00	140.50	211852	1.50	0.293		0.293
140.00	190.20	Chl; Epi; Ser <b>Chloritisation; Epidotisation; Sericitisation</b> redish to greenish porph syenite chloritized-epidotized-sericitized segments x-cutting the syenite moderated chloritization on porph, dark chlorite vns and vits2% qtz-carb vts 2-3%. From 152.7-153.3: foliated syenite, porph still visible, sericite-epitode-chl alt	140.50	142.00	211853	1.50	1.005		1.005
			142.00	143.50	211854	1.50	0.168		0.168
			143.50	145.00	211855	1.50	0.015		0.015
			145.00	146.50	211856	1.50	0.017		0.017
			146.50	148.00	211857	1.50	0.009		0.009
			148.00	149.50	211858	1.50	<0.005		0.001
			149.50	151.00	211859	1.50	0.013		0.013
150.50	153.20	Py03 <b>Pyrite 03%</b> 2-3% ammalgamated py, mostly on qtz-carb veins	151.00	152.50	211860	1.50	0.029		0.029
			152.50	154.00	211861	1.50	0.018		0.018
153.20	190.20	Py01 <b>Pyrite 01%</b> diss py up to 5% very locally, mostly trace of py	154.00	155.50	211862	1.50	0.318		0.318
			155.50	157.00	211863	1.50	0.041		0.041
			157.00	158.50	211864	1.50	0.009		0.009
			158.50	160.00	211865	1.50	0.262		0.262
			160.00	161.50	211866	1.50	0.309		0.309
			161.50	163.00	211867	1.50	0.005		0.005
162.20	166.90	AN <b>Trachyte</b> Trachytic dyke  From 162.2-162.9m: trachytic dyke, 30 % porph(from 5-10mm) From 162.9-164m: redish porph syenite From 164-166.9m: trachytic dyke, 30% poprh (from 10-20mm). 3% qtz-carb and chlorite veins 35TCA.	163.00	164.50	211868	1.50	<0.005		0.001
			164.50	166.00	211869	1.50	0.235		0.235
			166.00	167.50	211871	1.50	0.013		0.013
166.90	170.70	SY <b>Syenite</b> redish syenite, chl-sericite-epitode alt x-cutting the syenite. 2%chl veins 35-45TCA 2% qtz-carb veins 60-80TCA	167.50	169.00	211872	1.50	0.029		0.029
			169.00	170.50	211873	1.50	0.046		0.046
			170.50	172.00	211874	1.50	0.119		0.119



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
170.70	190.20	2% porph.chlorite alt, from 5-15mm At 168.7m: fault 45TCA. qtz veins not fitting							
		SY; POR	172.00	173.50	211875	1.50	0.121		0.121
		<b>Syenite; Porphyric</b>	173.50	175.00	211876	1.50	0.377		0.377
		redish porph syenite	175.00	176.50	211877	1.50	0.058		0.058
		7% porph, chloritized rim, from 5-30mm mostly 10-15mm	176.50	178.00	211878	1.50	0.087		0.087
		1% qtz-carb veins	178.00	179.50	211879	1.50	0.009		0.009
		1% dark chlorite veins 30TCA	179.50	181.00	211880	1.50	0.101		0.101
		From 170.8-171.3m: breccia parallele to core, chloritic matrix, redish syenite clasts, sub-angular from 3-10mm (mostly 5mm)	181.00	182.50	211881	1.50	0.170		0.170
		1% of cm qtz-fds-carb-chlorite veins 40TCA	182.50	184.00	211882	1.50	0.036		0.036
			184.00	185.50	211883	1.50	0.044		0.044
	185.50	187.00	211884	1.50	0.039		0.039		
	187.00	188.50	211885	1.50	0.036		0.036		
	188.50	190.00	211886	1.50	0.261		0.261		
	190.00	191.50	211887	1.50	2.560		2.560		
190.20	192.00	SY; MNZD							
		<b>Syenite; Mineralized</b>							
		strong sil grey veins x-cutting the redish porph syenite							
		very fine diss py in silicified veins and in matrix							
		10% sil veins, up to 5cm wide. milky qtz.							
		5% chloritized porph from 5-30mm.							
190.20	192.00	Chl; Sil							
		<b>Chloritisation; Silicification</b>							
		strong sil grey veins x-cutting the redish porph syenite							
190.20	192.00	Py05	191.50	193.00	211888	1.50	3.110	2.94	2.940
		<b>Pyrite 05%</b>							
		grey sil veins x-cutting the syenite							
		From 3-7% of very fine py diss in sil veins and in redish syenite matrix							
192.00	209.50	SY; POR							
		<b>Syenite; Porphyric</b>							
		redish locally greenish porph syenite							
		porph: from 5-10%, from 5-30mm mostly 10mm. moderate chloritisation							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
192.00	209.50	on porph week diss py 1-2%chl vits, 40TCA qtz-carb veins 1-2%. 1% cm qtz-fds-carb-chl veins  EOH : 209.5m Chl; Epi; Ser <b>Chloritisation; Epidotisation; Sericitisation</b> moderate chloritized porph epidotized-sericitized segments x-cutting the redish porph syenite							
192.00	209.50	Py01 <b>Pyrite 01%</b> mostly traces of py, up to 5 very locally diss and ammalgamated(when ammalgamated its usually on qtz-carb veins)	193.00	194.50	211889	1.50	0.035		0.035
			194.50	196.00	211891	1.50	0.035		0.035
			196.00	197.50	211892	1.50	0.097		0.097
			197.50	199.00	211893	1.50	0.062		0.062
			199.00	200.50	211894	1.50	0.124		0.124
			200.50	202.00	211895	1.50	0.024		0.024
			202.00	203.50	211896	1.50	0.050		0.050
			203.50	205.00	211897	1.50	0.038		0.038
			205.00	206.50	211898	1.50	0.005		0.005
			206.50	208.00	211899	1.50	<0.005		0.001
			208.00	209.50	211901	1.50	0.026		0.026
209.50	Fin du sondage Nombre d'échantillons : 140 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 208.70								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
25.00	26.50	211770	O61d	1.50	4.810	4.780
53.50	55.00	211790	O54Pa	1.50	3.030	3.030
67.00	68.50	211800	m	1.50	<0.005	0.001
80.50	82.00	211810	O6Pc	1.50	1.575	1.575
109.00	110.50	211830	O50Pb	1.50	0.877	0.877
133.00	134.50	211847	O61d	1.50	4.960	4.720
136.00	137.50	211850	m	1.50	<0.005	0.001
164.50	166.00	211870	O54Pa	1.50	2.700	2.700
193.00	194.50	211890	O6Pc	1.50	1.595	1.595
206.50	208.00	211900	m	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-96

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : Surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : Carl Corriveau

Du : 2009-12-02

Date de description : 2009-12-05

Au : 2009-12-04

Collet

UTM

Azimut : 182.20°

Plongée : -44.70°

Longueur : 168.00 m

Est 631 006.5

Nord 5 374 440.6

Élévation 309.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	180.00°	-45.00°	Non
Reflex	6.00	180.70°	-44.90°	Non
Reflex	9.00	182.20°	-44.90°	Non
Reflex	12.00	184.00°	-44.80°	Oui
Reflex	15.00	183.40°	-44.90°	Non
Reflex	18.00	183.70°	-44.90°	Non
Reflex	21.00	183.80°	-44.80°	Non
Reflex	24.00	183.20°	-45.00°	Non
Reflex	27.00	184.00°	-44.90°	Non
Reflex	30.00	183.70°	-44.80°	Non
Reflex	33.00	183.20°	-44.70°	Non
Reflex	36.00	183.60°	-44.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	182.80°	-44.70°	Non
Reflex	42.00	183.00°	-44.80°	Non
Reflex	45.00	183.80°	-44.90°	Non
Reflex	48.00	183.90°	-44.80°	Non
Reflex	51.00	183.90°	-44.80°	Non
Reflex	54.00	184.10°	-44.80°	Oui
Reflex	57.00	183.00°	-44.70°	Non
Reflex	60.00	182.80°	-44.80°	Non
Reflex	63.00	182.90°	-44.80°	Non
Reflex	66.00	183.70°	-44.80°	Non
Reflex	69.00	183.50°	-44.80°	Non
Reflex	72.00	183.40°	-44.80°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All downhole survey corrected for mag declinaison -12.5W

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	184.00°	-44.80°	Non					
Reflex	78.00	184.20°	-44.80°	Non					
Reflex	81.00	184.60°	-44.70°	Non					
Reflex	84.00	184.10°	-44.80°	Non					
Reflex	87.00	184.00°	-44.70°	Non					
Reflex	90.00	183.70°	-44.70°	Non					
Reflex	93.00	184.40°	-44.80°	Oui					
Reflex	96.00	183.50°	-44.60°	Non					
Reflex	99.00	183.80°	-44.60°	Non					
Reflex	102.00	184.70°	-44.70°	Non					
Reflex	105.00	184.60°	-44.70°	Non					
Reflex	108.00	185.10°	-44.70°	Non					
Reflex	111.00	185.40°	-44.70°	Non					
Reflex	114.00	185.10°	-44.60°	Non					
Reflex	117.00	184.80°	-44.60°	Non					
Reflex	120.00	184.10°	-44.60°	Non					
Reflex	123.00	184.70°	-44.60°	Non					
Reflex	126.00	184.90°	-44.70°	Non					
Reflex	129.00	185.20°	-44.80°	Non					
Reflex	132.00	185.60°	-44.70°	Non					
Reflex	135.00	185.90°	-44.70°	Non					
Reflex	138.00	185.10°	-44.60°	Non					
Reflex	141.00	185.50°	-44.60°	Non					
Reflex	144.00	185.50°	-44.60°	Non					
Reflex	147.00	184.90°	-44.60°	Non					
Reflex	150.00	185.70°	-44.70°	Non					
Reflex	153.00	185.40°	-44.50°	Non					
Reflex	156.00	185.40°	-44.50°	Non					
Reflex	159.00	185.60°	-44.60°	Non					
Reflex	162.00	186.20°	-44.50°	Non					
Reflex	165.00	186.00°	-44.60°	Non					
Reflex	168.00	186.50°	-44.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.70	SY; POR <b>Syenite; Porphyric</b> From 2.1 to 2.7, 60 cm of core NW recuperate from casing. All core sent to lab for analysis sample number 226265							
0.00	21.50	Py0.5; Hm <b>Pyrite 0.5%; Hematite</b> Overall traces disseminated Py. Traces Hm disseminated and veins.  Short dm segments and veins mineralized 3% Py disseminated and clusters 14.8-15.1m 19-19.15m	2.10	2.70	226265	0.60	<0.005		0.001
2.70	21.50	SY <b>Syenite</b> Redish mottled syenite. Generally magnetic. 5% white silica-Qz veins. 3% white carbonates veinlets spider web texture. 5% partially chloritized feldspars porphyries. Short dm segments and veins mineralized 3% Py (19-19.15m)  2cm silica-carb-hm-py veins and breccia veins: 18.8-18.9m 25 TCA 19.4m 40-60 TCA  Sharp lower contact marked by increasing Silica alteration							
2.70	21.50	Chl <b>Chloritisation</b> Week chlorite porphyries altered	2.70	4.50	226266	1.80	0.018		0.018
			4.50	6.00	226267	1.50	0.011		0.011
			6.00	7.50	226268	1.50	0.026		0.026
			7.50	9.00	226269	1.50	0.005		0.005
			9.00	10.50	226271	1.50	0.007		0.007
			10.50	12.00	226272	1.50	0.005		0.005
			12.00	13.50	226273	1.50	0.010		0.010
			13.50	15.00	226274	1.50	0.006		0.006
			15.00	16.50	226275	1.50	0.013		0.013
			16.50	18.00	226276	1.50	0.069		0.069
			18.00	19.50	226277	1.50	0.344		0.344
			19.50	21.00	226278	1.50	0.067		0.067
			21.00	22.50	226279	1.50	0.570		0.570

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
21.50	25.60	SY; BX; MNZD <b>Syenite; Breccia; Mineralized</b> Grey with greenish redish segments silicified and brecciated mineralized syenite.						
21.50	25.60	Sil; Ser <b>Silicification; Sericitisation</b> Pervasive silicification discoloring and locally brecciating the syenite 5-10% Green sericite veinlets hailine texture and veins Minor chlorite veinlets and porphyries altered  22.6-23m strongly sericitized. Green sericites veinlets and veins 30 TCA						
21.50	25.60	Py05 <b>Pyrite 05%</b> Up to 5 % fine Py disseminated and clusters in matrix and veins.	22.50	24.00	226281	1.50	0.402	0.402
			24.00	25.50	226282	1.50	1.695	1.695
			25.50	27.00	226283	1.50	0.680	0.680
25.60	30.90	SY <b>Syenite</b> Red mottled syenite. 5% blackish chglorite veins/veinlets and brecciated veins. not mag.						
25.60	30.90	Ser; Chl <b>Sericitisation; Chloritisation</b> Minor green sericite hailine texture. 5% blackish chlorite veins and veinlets all directions.						
25.60	30.90	Py0.5 <b>Pyrite 0.5%</b> traces fine diss Py	27.00	28.50	226284	1.50	0.011	0.011
			28.50	30.00	226285	1.50	0.005	0.005
			30.00	31.50	226286	1.50	0.012	0.012
30.90	33.30	SY; MNZD <b>Syenite; Mineralized</b> Pale red mottled partially silicified and mineralized. 2-3% Py disseminated and clusters. 3% white qz-carb veins.						
30.90	33.30	Sil <b>Silicification</b> Partially silicified segment discoloring primary red syenite to pale red.						
30.90	33.30	Py03 <b>Pyrite 03%</b> 3% Py disseminated and clusters	31.50	33.00	226287	1.50	0.018	0.018
			33.00	34.50	226288	1.50	0.018	0.018

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
33.30	42.20	SY; POR <b>Syenite; Porphyric</b> Rusty upper contact. Purple redish porphyritic syenite. 5% 5mm and + feldspars porphyries partially chloritized and chl patches. 4% Greenish hairline sericite veinlets.						
33.30	42.20	Ser; Chl <b>Sericitisation; Chloritisation</b> Moderate Chloritisation. 5% 5mm and + feldspars porphyries partially chloritized and chl patches.  Moderate Sericitisation: 4% Greenish hairline sericite veinlets.						
33.30	42.20	Py0.5 <b>Pyrite 0.5%</b> traces disseminated Py.	34.50	36.00	226289	1.50	0.018	0.018
			36.00	37.50	226291	1.50	0.024	0.024
			37.50	39.00	226292	1.50	0.055	0.055
			39.00	40.50	226293	1.50	0.097	0.097
			40.50	42.00	226294	1.50	0.138	0.138
			42.00	43.50	226295	1.50	0.363	0.363
42.20	68.30	SY; POR; MNZD <b>Syenite; Porphyric; Mineralized</b> Purple grey greenish to redish partially silicified and mineralized porphyritic syenite.  Patchy grey purple segments and veins 5-10% fine disseminated, stringers and clusters Py. Pale discolorate redish segment: 3% Py  5-8% Fp porphyries partially sericitized and chloritized. 10% white silica veins and brecciated veins.  44.3-49.1: Minor oxydized fault zone. 49.1m: 10 cm sub parallel TCA vuggy Qz Veins 2-4mm. Vugs and drusy Qz  Generally, Py is associate with silica altération. The more silica you have, the more sulphide content increase. Also sulphides in chloritized fractures ans por along bottom contact.						



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
42.20	66.90	Sil; Ser; Chl <b>Silicification; Sericitisation; Chloritisation</b> 60% Partially silicified, pervasive Si. 20% Apple green sericitized patch 10% Chloritized fractures and Fp porphyries altered.  44.3-49.1m: 5-10% rusty oxydation (limonite)						
42.20	68.30	Py05 <b>Pyrite 05%</b> Patchy grey purple segments and veins 5-10% fine disseminated, stringers and clusters Py. Pale discolored redish segments: 3% Py	43.50	45.00	226296	1.50	0.492	0.492
44.30	49.10	FZ; BC; FOL; FRA <b>Fault Zone; Broken core; Foliation ; Fractured</b> Very oxydized rusty fractured broken core. Minor Fault zone. Sharp lower contact	45.00	46.50	226297	1.50	0.058	0.058
			46.50	48.00	226298	1.50	0.355	0.355
			48.00	49.50	226299	1.50	1.045	1.045
			49.50	51.00	226300	1.50	0.442	0.442
			51.00	52.50	226301	1.50	0.373	0.373
			52.50	54.00	226302	1.50	0.084	0.084
			54.00	55.50	226303	1.50	0.244	0.244
			55.50	57.00	226304	1.50	0.103	0.103
			57.00	58.50	226305	1.50	0.071	0.071
			58.50	60.00	226306	1.50	0.277	0.277
			60.00	61.50	226307	1.50	0.126	0.126
			61.50	63.00	226308	1.50	0.240	0.240
			63.00	64.50	226309	1.50	0.166	0.166
			64.50	66.00	226311	1.50	0.130	0.130
			66.00	67.50	226312	1.50	0.045	0.045
66.90	70.25	Ser; Chl; Sil <b>Sericitisation; Chloritisation; Silicification</b> Massive Sericite-Chl pervasive alteration. Minor Silicified patches remaining.	67.50	69.00	226313	1.50	0.152	0.152
68.30	70.25	TZ; FOL <b>Transitional Zone; Foliation</b> Green very altered transitional zone. Foliation 50 to 70 TCA. Elongate						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
68.30	70.25	Py02 4% pink white FP-Carb veins. <b>Pyrite 02%</b> 2% disseminated and disseminated clusters.	69.00	70.50	226314	1.50	0.294		0.294
70.25	104.90	SY; POR <b>Syenite; Porphyric</b> Transitional upper contact Redish porphyritic syenite. 5-10% 5mm to 2cm porphyries (mostly 1cm). Partially sericitized and chloritized porphyries. 3% white Qz carb veinsl.  Short mineralized veins and segments: Py 3% disseminated. Partially silicified segments and Qz-silica veins: 78.8-78.95m 84.2-84.25m 85.35-85.70m							
70.25	113.20	Ser; Chl <b>Sericitisation; Chloritisation</b> Pervasive strong sericite and moderate chloritized porphyries and veinlets.  Short partially silicified segments.	70.50	72.00	226315	1.50	0.019		0.019
			72.00	73.50	226316	1.50	0.015		0.015
			73.50	75.00	226317	1.50	0.026		0.026
			75.00	76.50	226318	1.50	0.019		0.019
			76.50	78.00	226319	1.50	0.009		0.009
			78.00	79.50	226320	1.50	0.032		0.032
			79.50	81.00	226321	1.50	0.010		0.010
			81.00	82.50	226322	1.50	0.058		0.058
			82.50	84.00	226323	1.50	0.050		0.050
			84.00	85.50	226324	1.50	0.022		0.022
			85.50	87.00	226325	1.50	0.043		0.043
			87.00	88.50	226326	1.50	0.013		0.013
			88.50	90.00	226327	1.50	0.016		0.016
			90.00	91.50	226328	1.50	0.010		0.010
			91.50	93.00	226329	1.50	0.024		0.024
			93.00	94.50	226331	1.50	0.029		0.029
			94.50	96.00	226332	1.50	0.010		0.010
			96.00	97.50	226333	1.50	0.013		0.013

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
70.25	104.90	Py; Hm <b>Pyrite ; Hematite</b> Overall traces disseminated Py.  Short mineralized veins and segments: Py 3% disseminated. Partially silicified segments and Qz-silica veins: 78.8-78.95m 84.2-84.25m 85.35-85.70m  Hematite cluster in veins. Saccaroidale Qz, silica, calcite, chlorite and mineralized (Py-Hm) 5mm to 2cm tension veins. 87.2m, 92.4m, 96.55m, 96.8m, 96.87m, 97.4m, 97.7m	97.50	99.00	226334	1.50	0.012		0.012
			99.00	100.50	226335	1.50	0.008		0.008
			100.50	102.00	226336	1.50	0.006		0.006
			102.00	103.50	226337	1.50	0.005		0.005
			103.50	105.00	226338	1.50	0.010		0.010
104.90	113.20	SY; FW <b>Syenite; Elongated Fragments</b> Green strongly sericitized and chloritized syenite. 5% pinkish white Qz-fp-(+limonite) veins. 3% dark green chlorite veins 2% grey silica veins  1-2% elongate strongly chl por  lower contact: 40cm chloritized matrix breccia							
104.90	113.20	Py <b>Pyrite</b> 1-2% 2mm Py clusters associate with silica veins (ex:111.25m) Partially Si segment 109.7m-110.3m 3% very fine Py disseminated	105.00	106.50	226339	1.50	0.011		0.011
			106.50	108.00	226341	1.50	0.120		0.120
			108.00	109.50	226342	1.50	0.267		0.267
			109.50	111.00	226343	1.50	0.248		0.248
			111.00	112.50	226344	1.50	0.036		0.036

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
113.20	168.00	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic syenite. 5 to 10% 5mm to 2cm (average 1cm) partially to totally chloritized and/or sericitized feldspars porphyries. 3-5% white green sericite-carbonates veinlets spider web texture.	112.50	114.00	226345	1.50	0.010		0.010
113.20	168.00	Ser; Chl <b>Sericitisation; Chloritisation</b> Moderate sericite pervasive veinlets and partially altering porphyries.. Week Chl : veinlets and partially altered porphyries Shorts segments partially Silicified	114.00	115.50	226346	1.50	0.009		0.009
			115.50	117.00	226347	1.50	0.124		0.124
			117.00	118.50	226348	1.50	0.159		0.159
			118.50	120.00	226349	1.50	0.006		0.006
			120.00	121.50	226351	1.50	0.114		0.114
			121.50	123.00	226352	1.50	0.045		0.045
			123.00	124.50	226353	1.50	0.045		0.045
			124.50	126.00	226354	1.50	0.015		0.015
			126.00	127.50	226355	1.50	0.021		0.021
			127.50	129.00	226356	1.50	0.036		0.036
113.20	129.00	Py <b>Pyrite</b> Traces Py							
129.00	140.50	Py03 <b>Pyrite 03%</b> 3-4% Dark grey silica+Py veins 30TCA	129.00	130.50	226357	1.50	0.388		0.388
			130.50	132.00	226358	1.50	0.310		0.310
			132.00	133.50	226359	1.50	0.319		0.319
			133.50	135.00	226360	1.50	0.247		0.247
			135.00	136.50	226361	1.50	0.189		0.189
			136.50	138.00	226362	1.50	0.714		0.714
			138.00	139.50	226363	1.50	1.405		1.405
			139.50	141.00	226364	1.50	0.519		0.519
140.50	168.00	Hm; Py <b>Hematite ; Pyrite</b> 1% disseminated Py 3% White Qz-Hm veins. Specular hematite 15-50% in veins. Blackish mineralized veinlets and veins: 3% Py traces Hm in partially Si segments (ex: 150-151.3m)	141.00	142.50	226365	1.50	0.180		0.180
			142.50	144.00	226366	1.50	0.010		0.010
			144.00	145.50	226367	1.50	0.019		0.019
			145.50	147.00	226368	1.50	0.034		0.034
			147.00	148.50	226369	1.50	0.185		0.185
			148.50	150.00	226371	1.50	0.487		0.487

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	150.00	151.50	226372	1.50	0.621		0.621
	151.50	153.00	226373	1.50	0.007		0.007
	153.00	154.50	226374	1.50	0.036		0.036
	154.50	156.00	226375	1.50	<0.005		0.001
	156.00	157.50	226376	1.50	<0.005		0.001
	157.50	159.00	226377	1.50	0.017		0.017
	159.00	160.50	226378	1.50	0.012		0.012
	160.50	162.00	226379	1.50	0.049		0.049
	162.00	163.50	226381	1.50	0.065		0.065
	163.50	165.00	226382	1.50	0.007		0.007
	165.00	166.50	226383	1.50	0.026		0.026
	166.50	168.00	226384	1.50	0.143		0.143
168.00	Fin du sondage Nombre d'échantillons : 111 Nombre d'échantillons QAQC : 9 Longueur totale échantillonnée : 165.90						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.50	9.00	226270	O6Pc	1.50	1.555	1.555
21.00	22.50	226280	m	1.50	<0.005	0.001
34.50	36.00	226290	O50Pb	1.50	0.863	0.863
63.00	64.50	226310	O54Pa	1.50	2.960	2.960
91.50	93.00	226330	O6Pc	1.50	1.575	1.575
105.00	106.50	226340	m	1.50	<0.005	0.001
118.50	120.00	226350	O50Pb	1.50	0.861	0.861
147.00	148.50	226370	O6Pc	1.50	1.615	1.615
160.50	162.00	226380	m	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-97

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : C. Gagnier

Du : 2009-11-27

Date de description : 2009-12-11

Au : 2009-12-02

Collet

Azimut : 178.17°

Plongée : -43.00°

Longueur : 225.10 m

UTM

Est 630 974.6

Nord 5 374 437.6

Élévation 310.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	170.00°	-45.00°	Oui
Reflex	6.00	180.60°	-43.80°	Non
Reflex	9.00	180.10°	-43.80°	Non
Reflex	12.00	180.70°	-43.90°	Non
Reflex	15.00	181.80°	-43.80°	Non
Reflex	18.00	181.30°	-43.90°	Non
Reflex	21.00	180.50°	-44.00°	Non
Reflex	24.00	181.10°	-43.90°	Non
Reflex	27.00	180.10°	-43.80°	Non
Reflex	30.00	179.80°	-44.00°	Non
Reflex	33.00	180.70°	-44.00°	Non
Reflex	36.00	181.60°	-43.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	180.30°	-44.00°	Non
Reflex	42.00	181.60°	-43.90°	Non
Reflex	45.00	181.80°	-43.90°	Non
Reflex	48.00	181.40°	-43.90°	Non
Reflex	51.00	181.70°	-43.80°	Non
Reflex	54.00	182.00°	-43.80°	Non
Reflex	57.00	181.10°	-43.70°	Non
Reflex	60.00	180.70°	-43.70°	Non
Reflex	63.00	181.00°	-43.70°	Non
Reflex	66.00	180.60°	-43.70°	Non
Reflex	69.00	181.30°	-43.70°	Non
Reflex	72.00	181.20°	-43.70°	Non

Description

GPS Datum NAD83, UTM Zone 17.

The Reflex deviation tests were corrected for magnetic declination (12.5 degrees to the west). A multi-shot is stored on the network.

A 0.9m sample was recovered from the casing and sent to the lab (212813).

Hole surveyed December 7, 2009 by Descarreaux.

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	180.90°	-43.70°	Non	Reflex	174.00	183.20°	-43.20°	Non
Reflex	78.00	180.90°	-43.70°	Non	Reflex	177.00	183.30°	-43.20°	Non
Reflex	81.00	182.60°	-43.70°	Non	Reflex	180.00	184.00°	-43.20°	Non
Reflex	84.00	182.30°	-43.70°	Non	Reflex	183.00	184.30°	-43.20°	Non
Reflex	87.00	182.30°	-43.70°	Non	Reflex	186.00	185.40°	-43.00°	Oui
Reflex	90.00	182.20°	-43.50°	Non	Reflex	189.00	183.40°	-43.00°	Non
Reflex	93.00	181.20°	-43.50°	Non	Reflex	192.00	184.00°	-43.10°	Non
Reflex	96.00	182.20°	-43.70°	Non	Reflex	195.00	184.10°	-43.10°	Non
Reflex	99.00	182.20°	-43.50°	Non	Reflex	198.00	183.90°	-42.90°	Non
Reflex	102.00	181.70°	-43.40°	Non	Reflex	201.00	184.10°	-42.90°	Non
Reflex	105.00	181.40°	-43.50°	Non	Reflex	204.00	183.20°	-42.90°	Non
Reflex	108.00	181.30°	-43.40°	Non	Reflex	207.00	184.00°	-43.00°	Non
Reflex	111.00	182.50°	-43.50°	Non	Reflex	210.00	185.00°	-42.90°	Non
Reflex	114.00	182.50°	-43.30°	Non	Reflex	213.00	184.80°	-42.80°	Non
Reflex	117.00	183.10°	-43.40°	Non	Reflex	216.00	184.70°	-42.70°	Non
Reflex	120.00	182.70°	-43.30°	Non	Reflex	219.00	184.60°	-42.90°	Non
Reflex	123.00	181.50°	-43.30°	Non	Reflex	222.00	185.40°	-42.80°	Non
Reflex	126.00	182.40°	-43.50°	Non	Reflex	225.00	184.70°	-42.90°	Non
Reflex	129.00	183.10°	-43.50°	Non					
Reflex	132.00	183.60°	-43.40°	Non					
Reflex	135.00	183.20°	-43.30°	Non					
Reflex	138.00	183.00°	-43.20°	Non					
Reflex	141.00	182.70°	-43.50°	Non					
Reflex	144.00	182.90°	-43.40°	Non					
Reflex	147.00	183.20°	-43.30°	Non					
Reflex	150.00	183.00°	-43.20°	Non					
Reflex	153.00	182.90°	-43.30°	Non					
Reflex	156.00	183.00°	-43.40°	Non					
Reflex	159.00	184.10°	-43.20°	Non					
Reflex	162.00	184.00°	-43.20°	Non					
Reflex	165.00	183.10°	-43.10°	Non					
Reflex	168.00	182.90°	-43.20°	Non					
Reflex	171.00	183.30°	-43.30°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.10	MT <b>overburden</b>						
2.10	24.90	SY POR; MAS <b>Syenite Porphyry Intrusive; Massive rock</b> 90cm of core from the casing have been collected, assumed to be from the outcrop (3.0m- 0.9m=2.1m) and sent completely to the lab (sample no 212813). Red brick, massive, not magnetic porphyry syenite with 10% of anhedral, 0.3 to 1cm (average: 0.5cm), white to greenish (when chloritized) K-feldspar phenocrysts. Cross-cut by 1% of 1-3mm white quartz-feldspar veinlets at 30 TCA. Sharp lower contact at 30 TCA.	2.10	3.00	212813	0.90	<0.005	0.001
			3.00	5.10	212814	2.10	0.096	0.096
			5.10	6.60	212816	1.50	0.005	0.005
			6.60	8.10	212817	1.50	0.015	0.015
			8.10	9.60	212818	1.50	<0.005	0.001
			9.60	11.10	212819	1.50	0.020	0.020
			11.10	12.60	212821	1.50	0.017	0.017
			12.60	14.10	212822	1.50	0.010	0.010
			14.10	15.60	212823	1.50	<0.005	0.001
			15.60	17.10	212824	1.50	<0.005	0.001
			17.10	18.60	212825	1.50	<0.005	0.001
			18.60	20.10	212826	1.50	<0.005	0.001
			20.10	21.60	212827	1.50	0.015	0.015
			21.60	23.10	212828	1.50	0.005	0.005
			23.10	24.90	212829	1.80	0.086	0.086
2.10	5.20	Wea <b>Weathering (Incl. Saprolitic alter.)</b> Brownish hematization.						
2.10	5.20	FRC <b>Fractured</b>						
24.90	51.40	SY; MNZ <b>Syenite; Mineralized</b> RW ZONE. Sharp contact at 30 TCA. Grey to reddish to greenish porphyry syenite, strongly silicified, moderately sericitized and carbonatized, not uniformly mineralized ( from 0% to 7% of fine pyrite). Cross-cut by 2% of white, anastomosed white feldspar-carbonate veinlets (at least 2 generations involved). Sharp lower contact at 40 TCA.						
24.90	51.40	Sil; Ser; Car <b>Silicification; Sericitisation; Carbonatisation</b>						
24.90	51.40	Py1.5 <b>Pyrite 1.5%</b>	24.90	26.10	212830	1.20	0.562	0.562

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
RW ZONE. Very heterogeneous mineralization: from 0% to 7% of fine pyrite.			26.10	27.60	212831	1.50	1.400		1.400
			27.60	29.10	212832	1.50	0.913		0.913
			29.10	30.60	212833	1.50	0.449		0.449
			30.60	32.10	212834	1.50	0.268		0.268
			32.10	33.60	212836	1.50	0.375		0.375
			33.60	35.10	212837	1.50	0.244		0.244
			35.10	36.60	212838	1.50	0.322		0.322
			36.60	38.10	212839	1.50	1.020		1.020
			38.10	39.60	212841	1.50	0.908		0.908
			39.60	41.10	212842	1.50	0.231		0.231
			41.10	42.60	212843	1.50	0.345		0.345
			42.60	44.10	212844	1.50	0.339		0.339
			44.10	45.60	212845	1.50	1.145		1.145
			45.60	47.10	212846	1.50	0.856		0.856
			47.10	48.60	212847	1.50	2.140		2.140
			48.60	50.10	212848	1.50	1.965		1.965
49.00	50.00	BRE	50.10	51.60	212849	1.50	0.039		0.039
<b>Breccia</b>									
Strongly brecciated. Faulted ?									
51.40	225.10	SY POR; MAS	51.60	53.10	212850	1.50	0.009		0.009
<b>Syenite Porphyry Intrusive; Massive rock</b>			53.10	54.60	212851	1.50	0.011		0.011
Sharp upper contact at 60 TCA. Red brick, massive, not magnetic			54.60	56.10	212852	1.50	0.007		0.007
multi-phase porphyry syenite with 15% of subhedral, white to red			56.10	57.60	212853	1.50	0.014		0.014
(hematized) or greenish (chloritized), 0.5 to 2cm (average: 0.8cm)			57.60	59.10	212854	1.50	0.028		0.028
often zoned, sometimes agglomerated K-feldspar phenocrysts in a red,			59.10	60.60	212856	1.50	0.009		0.009
aphanitic matrix. Cross-cut by less than 0.5% of millimetric			60.60	62.10	212857	1.50	0.010		0.010
quartz-chlorite-carbonate veinlets often at 40 TCA.									
End of hole at 224.1m									
61.90	63.40	Wea							
<b>Weathering (Incl. Saprolitic alter.)</b>									
Brown hematized zone.									
61.90	63.40	VEI;;Fp;;10°;;	62.10	63.60	212858	1.50	0.132		0.132
<b>Vein Feldspath (alkaline) 10°</b>			63.60	65.10	212859	1.50	0.088		0.088
15% of a flat white K-feldspar vein.			65.10	66.60	212861	1.50	0.015		0.015
			66.60	68.10	212862	1.50	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			68.10	69.60	212863	1.50		0.005		0.005
			69.60	71.10	212864	1.50		0.006		0.006
			71.10	72.60	212865	1.50		0.006		0.006
			72.60	74.10	212866	1.50		0.021		0.021
			74.10	75.60	212867	1.50		0.007		0.007
			75.60	77.10	212868	1.50		0.006		0.006
			77.10	78.60	212869	1.50		<0.005		0.001
			78.60	80.10	212870	1.50		<0.005		0.001
			80.10	81.60	212871	1.50		<0.005		0.001
			81.60	83.10	212872	1.50		0.006		0.006
			83.10	84.60	212873	1.50		<0.005		0.001
			84.60	86.10	212874	1.50		<0.005		0.001
			86.10	87.60	212876	1.50		<0.005		0.001
			87.60	89.10	212877	1.50		0.009		0.009
			89.10	90.60	212878	1.50		0.005		0.005
			90.60	92.10	212879	1.50		<0.005		0.001
			92.10	93.60	212881	1.50		<0.005		0.001
			93.60	95.10	212882	1.50		<0.005		0.001
			95.10	96.60	212883	1.50		0.010		0.010
			96.60	98.10	212884	1.50		<0.005		0.001
			98.10	99.60	212885	1.50		0.005		0.005
			99.60	101.10	212886	1.50		0.582		0.582
			101.10	102.60	212887	1.50		0.008		0.008
			102.60	104.10	212888	1.50		0.227		0.227
			104.10	105.60	212889	1.50		0.005		0.005
			105.60	107.10	212890	1.50		0.029		0.029
			107.10	108.60	212891	1.50		0.007		0.007
			108.60	110.10	212892	1.50		0.127		0.127
109.10	113.10	Chl Chloritisation								
109.10	113.10	VEI;;;80°;; Vein 80° 10% of white 2-3cm quartz veins at 70-85 TCA.	110.10	111.60	212893	1.50		0.818		0.818
			111.60	113.10	212894	1.50		0.039		0.039
			113.10	114.60	212896	1.50		0.355		0.355

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
117.00	118.00	FRC Fractured RQD=0	114.60	116.10	212897	1.50	0.349		0.349
			116.10	117.60	212898	1.50	0.009		0.009
			117.60	119.10	212899	1.50	0.138		0.138
			119.10	120.60	212901	1.50	0.025		0.025
			120.60	122.10	212902	1.50	0.007		0.007
			122.10	123.60	212903	1.50	0.009		0.009
			123.60	125.10	212904	1.50	0.079		0.079
			125.10	126.60	212905	1.50	0.631		0.631
			126.60	128.10	212906	1.50	1.090		1.090
			128.10	129.60	212907	1.50	0.080		0.080
			129.60	131.10	212908	1.50	0.085		0.085
			131.10	132.60	212909	1.50	0.020		0.020
			132.60	134.10	212910	1.50	0.185		0.185
			134.10	135.60	212911	1.50	0.544		0.544
			135.60	137.10	212912	1.50	0.571		0.571
139.25	139.40	LOST lost core Sample removed for F. Bouchard (Osisko).	137.10	138.60	212913	1.50	0.317		0.317
			138.60	140.10	212914	1.50	1.775		1.775
			140.10	141.60	212916	1.50	0.155		0.155
			141.60	143.10	212917	1.50	0.009		0.009
			143.10	144.60	212918	1.50	0.040		0.040
			144.60	146.10	212919	1.50	0.029		0.029
			146.10	147.60	212921	1.50	0.020		0.020
			147.60	149.10	212922	1.50	0.121		0.121
148.10	148.30	LOST lost core Lost core	149.10	150.60	212923	1.50	0.014		0.014
			150.60	152.10	212924	1.50	0.012		0.012
			152.10	153.60	212925	1.50	<0.005		0.001
			153.60	155.10	212926	1.50	0.005		0.005
			155.10	156.60	212927	1.50	0.222		0.222
			156.60	158.10	212928	1.50	0.057		0.057
			158.10	159.60	212929	1.50	1.280		1.280
159.95	160.05	LOST lost core	159.60	161.10	212930	1.50	0.012		0.012
			161.10	162.60	212931	1.50	0.011		0.011
			162.60	164.10	212932	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
163.60	165.40	I2D LT POR <b>Syenite Lath Porphyry Intrusive 40°</b> Sharp contacts at 40 TCA. Lath porphyry (trachyte) with 40% of 1cm white K-feldspar phenocrystals generally oriented at 40 TCA. Not mineralized.						
163.63	163.83	LOST <b>lost core</b> Sample removed for F. Bouchard (Osisko).	164.10	165.60	212933	1.50	0.193	0.193
			165.60	167.10	212934	1.50	0.024	0.024
			167.10	168.60	212936	1.50	0.008	0.008
			168.60	170.10	212937	1.50	0.033	0.033
			170.10	171.60	212938	1.50	0.185	0.185
			171.60	173.10	212939	1.50	0.367	0.367
			173.10	174.60	212941	1.50	0.197	0.197
			174.60	176.10	212942	1.50	0.013	0.013
			176.10	177.60	212943	1.50	0.236	0.236
			177.60	179.10	212944	1.50	0.539	0.539
			179.10	180.60	212945	1.50	0.062	0.062
			180.60	182.10	212946	1.50	0.015	0.015
			182.10	183.60	212947	1.50	0.041	0.041
			183.60	185.10	212948	1.50	0.495	0.495
			185.10	186.60	212949	1.50	0.847	0.847
			186.60	188.10	212950	1.50	0.258	0.258
			188.10	189.60	212951	1.50	0.158	0.158
189.60	190.10	VEI;3;Qz;T;15°;Au0.01Sp01Cp0.5; <b>Vein 3 Quartz Tension 15° Gold0.01% Sphalerite01%</b> <b>Chalcopyrite0.5%</b> A 3cm flat (15 degreesTCA) white quartz vein with 3 needle points of gold, 1% of yellow sphalerite and 0.5% of chalcopyrite.	189.60	191.10	212952	1.50	1.270	1.270
			191.10	192.60	212953	1.50	0.102	0.102
			192.60	194.10	212954	1.50	0.083	0.083
			194.10	195.60	212956	1.50	0.062	0.062
			195.60	197.10	212957	1.50	0.016	0.016
			197.10	198.60	212958	1.50	0.032	0.032
			198.60	200.10	212959	1.50	0.084	0.084
			200.10	201.60	212961	1.50	0.009	0.009
			201.60	203.10	212962	1.50	0.035	0.035
			203.10	204.60	212963	1.50	0.075	0.075
			204.60	206.10	212964	1.50	0.041	0.041
			206.10	207.60	212965	1.50	0.029	0.029

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	207.60	209.10	212966	1.50	0.015		0.015
	209.10	210.60	212967	1.50	0.020		0.020
	210.60	212.10	212968	1.50	0.045		0.045
	212.10	213.60	212969	1.50	0.042		0.042
	213.60	215.10	212970	1.50	0.164		0.164
	215.10	216.60	212971	1.50	0.078		0.078
	216.60	218.10	212972	1.50	0.017		0.017
	218.10	219.60	212973	1.50	0.016		0.016
	219.60	221.10	212974	1.50	0.028		0.028
	221.10	222.60	212976	1.50	0.018		0.018
	222.60	224.10	212977	1.50	0.018		0.018
225.10      Fin du sondage Nombre d'échantillons : 148 Nombre d'échantillons QAQC : 17 Longueur totale échantillonnée : 222.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.10	5.10	212815	O6Pc	0.00	1.535	1.535
11.10	11.10	212820	m	0.00	0.007	0.007
32.10	32.10	212835	O54Pa	0.00	2.970	2.970
38.10	38.10	212840	m	0.00	<0.005	0.001
59.10	59.10	212855	O50Pb	0.00	0.865	0.865
65.10	65.10	212860	m	0.00	<0.005	0.001
86.10	86.10	212875	O61d	0.00	4.840	4.920
92.10	92.10	212880	m	0.00	<0.005	0.001
113.10	113.10	212895	O6Pc	0.00	1.565	1.565
119.10	119.10	212900	m	0.00	<0.005	0.001
140.10	140.10	212915	O54Pa	0.00	2.970	2.970
146.10	146.10	212920	m	0.00	<0.005	0.001
167.10	167.10	212935	O50Pb	0.00	0.876	0.876
173.10	173.10	212940	m	0.00	<0.005	0.001
194.10	194.10	212955	O61d	0.00	4.810	4.940
200.10	200.10	212960	m	0.00	<0.005	0.001
221.10	221.10	212975	O6Pc	0.00	1.505	1.505

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-98

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : surface

Rang :

Place de travail : Beattie mine site

Foré par : foramex

Lot :

Décrit par : Maria Jose Comeau

Du : 2009-12-04

Date de description : 2009-12-10

Au : 2009-12-06

Collet

UTM

Azimut : 182.49°

Plongée : -45.00°

Longueur : 174.00 m

Est 631 029.6

Nord 5 374 447.7

Élévation 308.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	180.00°	-45.00°	Oui
Reflex	6.00	185.40°	-45.00°	Non
Reflex	9.00	185.30°	-45.00°	Non
Reflex	12.00	185.60°	-44.90°	Non
Reflex	15.00	183.30°	-44.80°	Non
Reflex	18.00	184.20°	-44.80°	Non
Reflex	21.00	182.50°	-44.80°	Oui
Reflex	24.00	185.40°	-44.80°	Non
Reflex	27.00	183.60°	-44.80°	Oui
Reflex	30.00	185.40°	-44.80°	Non
Reflex	33.00	185.10°	-45.00°	Non
Reflex	36.00	185.40°	-44.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	185.60°	-44.90°	Non
Reflex	42.00	184.90°	-44.90°	Non
Reflex	45.00	184.80°	-44.90°	Non
Reflex	48.00	184.40°	-45.00°	Non
Reflex	51.00	184.70°	-45.00°	Non
Reflex	54.00	184.60°	-45.10°	Non
Reflex	57.00	186.20°	-45.10°	Oui
Reflex	60.00	185.50°	-45.10°	Non
Reflex	63.00	185.20°	-45.10°	Non
Reflex	66.00	185.40°	-45.10°	Non
Reflex	69.00	186.80°	-45.00°	Non
Reflex	72.00	185.40°	-45.00°	Non

Description

GPS Datum NAD83, UTM Zone 17.

All downhole survey corrected for mag declinaison -12.5W

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	186.40°	-45.00°	Non	Reflex	174.00	191.80°	-44.70°	Non
Reflex	78.00	186.60°	-44.90°	Non					
Reflex	81.00	186.40°	-45.00°	Non					
Reflex	84.00	187.10°	-44.90°	Non					
Reflex	87.00	187.40°	-44.70°	Non					
Reflex	90.00	186.80°	-44.80°	Non					
Reflex	93.00	187.40°	-44.90°	Non					
Reflex	96.00	187.90°	-44.80°	Non					
Reflex	99.00	187.10°	-44.80°	Non					
Reflex	102.00	188.00°	-44.90°	Non					
Reflex	105.00	187.60°	-44.90°	Non					
Reflex	108.00	188.40°	-44.80°	Non					
Reflex	111.00	188.80°	-44.50°	Non					
Reflex	114.00	188.00°	-44.30°	Non					
Reflex	117.00	188.00°	-44.30°	Non					
Reflex	120.00	188.80°	-44.30°	Non					
Reflex	123.00	189.30°	-44.30°	Non					
Reflex	126.00	189.70°	-44.30°	Non					
Reflex	129.00	189.20°	-44.20°	Non					
Reflex	132.00	189.70°	-44.30°	Non					
Reflex	135.00	190.00°	-44.40°	Non					
Reflex	138.00	189.60°	-44.50°	Non					
Reflex	141.00	189.70°	-44.50°	Non					
Reflex	144.00	190.00°	-44.50°	Non					
Reflex	147.00	190.50°	-44.50°	Non					
Reflex	150.00	190.80°	-44.60°	Non					
Reflex	153.00	190.40°	-44.50°	Non					
Reflex	156.00	190.60°	-44.60°	Non					
Reflex	159.00	191.00°	-44.60°	Non					
Reflex	162.00	191.00°	-44.60°	Non					
Reflex	165.00	190.10°	-44.60°	Non					
Reflex	168.00	190.80°	-44.70°	Non					
Reflex	171.00	191.20°	-44.80°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.60	MT <b>Overburden</b>						
3.60	4.00	MT; I2D <b>Casing; Syenite</b> locally mineralized all sent to analysis						
3.60	42.80	Chl <b>Chloritisation</b> chlorite alt locally pervasive in matrix chloritized porph local chlorite veins local partial silicification	3.60	4.00	228133	0.40	0.006	0.006
3.60	5.60	Py01 <b>Pyrite 01%</b> traces of diss py						
4.00	7.60	SY <b>Syenite</b> redish-greenish mottled syenite 3% qtz-carb veins 1-2% chlorite vnlt traces of diss py, oxydized segments : From 5.6-6.1m, 5% of gost of euhedral py.	4.00	5.00	228134	1.00	0.006	0.006
			5.00	6.00	228135	1.00	0.019	0.019
5.60	6.10	Py05 <b>Pyrite 05%</b> From 5.6-6.1m, 5% of gost of euhedral py. oxydized zone	6.00	7.50	228136	1.50	0.007	0.007
6.10	23.50	Py01 <b>Pyrite 01%</b> traces of diss py	7.50	9.00	228137	1.50	0.007	0.007
7.60	33.20	SY; POR <b>Syenite; Porphyric</b> grey-greenish to redish porphyric syenite 3% qtz-carb veins 40TCA 1% chlorite vnlt porph: from 5-7% porph, from 5-10mm. pinkish-white and chloritized porph locally brecciated from 23.5-24m and oxydized 3% gost of py.	9.00	10.50	228138	1.50	<0.005	0.001
			10.50	12.00	228139	1.50	0.011	0.011
			12.00	13.50	228141	1.50	0.006	0.006
			13.50	15.00	228142	1.50	<0.005	0.001
			15.00	16.50	228143	1.50	0.005	0.005
			16.50	18.00	228144	1.50	0.009	0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			18.00	19.50	228145	1.50	<0.005		0.001
			19.50	21.00	228146	1.50	<0.005		0.001
			21.00	22.50	228147	1.50	<0.005		0.001
			22.50	24.00	228148	1.50	<0.005		0.001
23.50	24.00	Py03 <b>Pyrite 03%</b> locally brecciated from 23.5-24m and oxydized 3% gost of py.							
24.00	42.40	Py02 <b>Pyrite 02%</b> up to 2-3% diss py	24.00	25.50	228149	1.50	<0.005		0.001
			25.50	27.00	228151	1.50	0.008		0.008
			27.00	28.50	228152	1.50	0.007		0.007
			28.50	30.00	228153	1.50	<0.005		0.001
			30.00	31.50	228154	1.50	<0.005		0.001
			31.50	33.00	228155	1.50	0.127		0.127
			33.00	34.50	228156	1.50	0.042		0.042
33.20	42.40	SY <b>Syenite</b> light redish greenish mottled syenite 3% qtz-carb veins sub-parallel to core (up to 30TCA 3-5% faded greenish porph from 5-10mm	34.50	36.00	228157	1.50	<0.005		0.001
			36.00	37.50	228158	1.50	0.016		0.016
			37.50	39.00	228159	1.50	0.031		0.031
			39.00	40.50	228161	1.50	0.010		0.010
			40.50	42.00	228162	1.50	0.041		0.041
			42.00	43.50	228163	1.50	1.255		1.255
42.40	53.30	SY; POR <b>Syenite; Porphyric</b> grey sil porphyric syenite, slightly chloritized porph: 5% pinkish to white, locally chloritized, from 5-10mm qtz-carb veins 3% locally brecciated; qtz-carb matrix supported, sub angular clasts from 10-50mm redish syenite composition							
42.40	56.00	Py05 <b>Pyrite 05%</b> very fine diss py and in grey veins from 5-7%							
42.80	53.30	Sil; Chl <b>Silicification; Chloritisation</b> pervasive silicification local chloritized porph	43.50	45.00	228164	1.50	1.190		1.190
			45.00	46.50	228165	1.50	1.385		1.385
			46.50	48.00	228166	1.50	0.622		0.622
			48.00	49.50	228167	1.50	0.322		0.322

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
53.30	69.90	SY; MNZD <b>Syenite; Mineralized</b> redish to greenish locally mottled locally foliated oxydized segments in foliated areas. locally mineralized brecciated sil from : 62.1-63m, sub angular clasts, pinkish purpleish grey, mineralized 1% qtz-carb veins, traces of mineralized veins, 2% chlorite vnits 3-5% faded locally chloritized porph, from 5-15mm mostly less than 10mm. From 61.9m from 5% mineralisation	49.50	51.00	228168	1.50	0.112		0.112
			51.00	52.50	228169	1.50	0.563		0.563
			52.50	54.00	228170	1.50	0.484		0.484
			54.00	55.50	228171	1.50	0.541		0.541
			55.50	57.00	228172	1.50	0.020		0.020
53.30	62.10	Chl <b>Chloritisation</b> chloritized porph, chloritei vns local epidotisation-sericitisation							
56.00	61.90	Py02 <b>Pyrite 02%</b> diss py	57.00	58.50	228173	1.50	0.008		0.008
			58.50	60.00	228174	1.50	0.031		0.031
			60.00	61.50	228175	1.50	0.016		0.016
			61.50	63.00	228176	1.50	0.512		0.512
61.90	69.80	Py05 <b>Pyrite 05%</b> from 2-7% diss py, fine to very fine py oxydized foliated segments x-cutting the syenite Silicified segments x-cutting the syenite							
62.10	63.10	Sil; Ser; Epi <b>Silicification; Sericitisation; Epidotisation</b> silicified brecciated syenite pervasive sericitisation-epidotisation	63.00	64.50	228177	1.50	0.105		0.105
63.10	69.90	Chl; Epi; Ser <b>Chloritisation; Epidotisation; Sericitisation</b> chlorite vns and altered porph epidotisation-sericitisation in more foliated segments	64.50	66.00	228178	1.50	0.044		0.044
			66.00	67.50	228179	1.50	0.111		0.111
			67.50	69.00	228181	1.50	<0.005		0.001
			69.00	70.50	228182	1.50	0.161		0.161

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
69.80	75.70	Py07 <b>Pyrite 07%</b> from 5-10% very fine diss py in sil brecciated greyish-greenish syenite							
69.90	75.70	BX; I2D; MNZD <b>Breccia; Syenite; Mineralized</b> Sil bleached greenish-grey brecciated syenite qtz-carb matrix supporting clasts clasts from 5-100mm, sub angular, silicified grey and epidotized-sericitized clasts. 5% of 5mm white fds porph mineralised up to 10% very fine py.							
69.90	75.70	Sil; Epi; Ser; Chl <b>Silicification; Epidotisation; Sericitisation; Chloritisation</b> Fromsilicified breccia epidotizede-sericitized segments and porph chlortie vns	70.50	72.00	228183	1.50	0.520	3.27	0.520
			72.00	73.50	228184	1.50	1.020		1.020
			73.50	75.00	228185	1.50	1.025		1.025
			75.00	76.50	228186	1.50	3.200		3.270
75.70	91.50	SY; MNZD <b>Syenite; Mineralized</b> greenish to purple to greyish syenite locally porphyric: porph from 5-20mm, mostly 10mm. chloritized. 3-5% porph. locally foliated: chloritized elongated porph very locally brecciated: 1cm angular clasts in silicified segments 2% qtz-carb veins, 2% chlorite vnlt oxydized fractures From 82-83.2:milky qtz veins x-cutting a chloritized syenite, broken up core and oxydized. up to 7% mineralisation ps x-cutting a chlorite syenite							
75.70	91.50	Chl; Epi; Ser; Sil <b>Chloritisation; Epidotisation; Sericitisation; Silicification</b> chloritized segments with epidotized-sericitised local partial silicification chloritized porph chlortie vns							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
75.70	91.50	Py05 <b>Pyrite 05%</b> From 3-7% euhedral diss and amalgamated py	76.50	78.00	228187	1.50	0.581		0.581
			78.00	79.50	228188	1.50	0.054		0.054
			79.50	81.00	228189	1.50	0.064		0.064
			81.00	82.50	228190	1.50	0.452		0.452
			82.50	84.00	228191	1.50	1.580		1.580
			84.00	85.50	228192	1.50	0.424		0.424
			85.50	87.00	228193	1.50	0.444		0.444
			87.00	88.50	228194	1.50	0.366		0.366
			88.50	90.00	228195	1.50	0.086		0.086
			90.00	91.50	228196	1.50	0.069		0.069
91.50	105.30	SY <b>Syenite</b> redish mottled syenite very locally brecciated, 5mm angular clasts with qtz-carb and chlorite matrix 3-5% faded chloritized porph 2% chlorite veins 2% qtz-carb veins from traces up to 3% amalgamated py							
91.50	105.30	Chl <b>Chloritisation</b> redish syenite chloritized fated porphyries, 2% chlorite veins							
91.50	174.00	Py02 <b>Pyrite 02%</b> traces of diss py, up to 3% very locally amalgamated py at 124m up to 10% in grey veins 132.4-133.2m up to 5% diss euhedral py	91.50	93.00	228197	1.50	0.755		0.755
			93.00	94.50	228198	1.50	0.043		0.043
			94.50	96.00	228199	1.50	0.022		0.022
			96.00	97.50	228201	1.50	<0.005		0.001
			97.50	99.00	228202	1.50	0.005		0.005
			99.00	100.50	228203	1.50	<0.005		0.001
			100.50	102.00	228204	1.50	0.138		0.138
			102.00	103.50	228206	1.50	<0.005		0.001
			103.50	105.00	228207	1.50	0.012		0.012
			105.00	106.50	228208	1.50	0.023		0.023
105.30	111.00	SY; FOL <b>Syenite; Foliation</b>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
105.30	106.20	chloritized foliated syenite chloritized elongated porph 5% porph traces of diss py 1% qtz-carb veins 1% chlorite vntls Chl; Ser; Pot <b>Chloritisation; Sericitisation; Potassic alteration</b> chloritized-sericitized syenite x-cutted by pinkish (potassic) alteration							
106.20	120.10	Chl; Epi; Ser; Pot <b>Chloritisation; Epidotisation; Sericitisation; Potassic alteration</b> pervasive chloritisation and chloritised porph and veins 2% pinkish veins, fds(k)-qtz-carb veins up to 5cm wide epidotized-sericitized pervasive and x-cutting	106.50	108.00	228209	1.50	0.149		0.149
			108.00	109.50	228210	1.50	0.039		0.039
			109.50	111.00	228211	1.50	0.015		0.015
111.00	120.10	SY <b>Syenite</b> greenish purplish pinkish syenite locally porphyric; 5-7% less than 1cm white and chloritized porph brecciated look caused by a great amount of qtz-carb/chlorite and fds(k) veins 5% fds(k)-qtz-carb-chlorite veins ( up to 5cm wide ) qtz-carb veins-30TCA fds(k)-qtz-carb-35TCA	111.00	112.50	228212	1.50	0.038		0.038
			112.50	114.00	228213	1.50	3.320	3.34	3.340
			114.00	115.50	228214	1.50	0.805		0.805
			115.50	117.00	228215	1.50	0.008		0.008
			117.00	118.50	228216	1.50	0.106		0.106
			118.50	120.00	228217	1.50	0.023		0.023
			120.00	121.50	228218	1.50	0.018		0.018
120.10	174.00	SY; POR <b>Syenite; Porphyric</b> redish porph syenite porph: From 120.1-132.5: mostly chloritized porph, 3-5% porph, from 5-15mm. From 132.5-138: mostly white fds porph, 5%, from 5-30mm mostly 10mm. From 138-174m: mostly white pinkish porph locally with chloritized rim, 5% porph, 5-30mm. mostly 10- 15mm. 2% qtz-carb veins 1% chlorite vlts locally epidotized-sericitized syenite x-cutting the redish syenite locally brecciated with qtz-carb matrix, 5mm angular clasts 2-3cm wide brecciated zone							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
From 126.1-127: milky qtz veins sub parallel to sericitized syenite. 1-2% amalgamated py.								
EOH : 174m								
120.10	174.00	Chl	121.50	123.00	228219	1.50	0.028	0.028
		<b>Chloritisation</b>	123.00	124.50	228221	1.50	0.338	0.338
		redish porphyric syenite	124.50	126.00	228222	1.50	0.007	0.007
		chloritized porph and vns	126.00	127.50	228223	1.50	<0.005	0.001
		sercitised-epidotised segments x-cutting the redish syenite;	127.50	129.00	228224	1.50	0.106	0.106
		From 126.1-127m / 131.6-131.8m/132.3-132.5m	129.00	130.50	228225	1.50	0.034	0.034
			130.50	132.00	228226	1.50	0.134	0.134
			132.00	133.50	228227	1.50	0.025	0.025
			133.50	135.00	228228	1.50	0.048	0.048
			135.00	136.50	228229	1.50	0.050	0.050
			136.50	138.00	228230	1.50	0.040	0.040
			138.00	139.50	228231	1.50	0.048	0.048
			139.50	141.00	228232	1.50	0.462	0.462
			141.00	142.50	228233	1.50	1.065	1.065
			142.50	144.00	228234	1.50	0.240	0.240
			144.00	145.50	228235	1.50	0.007	0.007
			145.50	147.00	228236	1.50	0.118	0.118
			147.00	148.50	228237	1.50	0.114	0.114
			148.50	150.00	228238	1.50	<0.005	0.001
			150.00	151.50	228239	1.50	0.057	0.057
			151.50	153.00	228241	1.50	0.163	0.163
			153.00	154.50	228242	1.50	0.355	0.355
			154.50	156.00	228243	1.50	1.020	1.020
			156.00	157.50	228244	1.50	0.026	0.026
			157.50	159.00	228245	1.50	0.013	0.013
			159.00	160.50	228246	1.50	0.025	0.025
			160.50	162.00	228247	1.50	0.005	0.005
			162.00	163.50	228248	1.50	0.019	0.019
			163.50	165.00	228249	1.50	0.435	0.435
			165.00	166.50	228251	1.50	0.099	0.099



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	166.50	168.00	228252	1.50	0.225		0.225
	168.00	169.50	228253	1.50	0.075		0.075
	169.50	171.00	228254	1.50	0.010		0.010
	171.00	172.50	228255	1.50	0.015		0.015
	172.50	174.00	228256	1.50	0.023		0.023
174.00	Fin du sondage Nombre d'échantillons : 115 Nombre d'échantillons QAQC : 9 Longueur totale échantillonnée : 170.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.50	12.00	228140	O6Pc	1.50	1.625	1.625
24.00	25.50	228150	m	1.50	<0.005	0.001
37.50	39.00	228160	O50Pb	1.50	0.879	0.879
66.00	67.50	228180	O54Pa	1.50	2.870	2.870
94.50	96.00	228200	m	1.50	<0.005	0.001
100.50	102.00	228205	O61d	1.50	4.840	5.280
121.50	123.00	228220	O6Pc	1.50	1.570	1.570
150.00	151.50	228240	O54Pa	1.50	2.930	2.930
163.50	165.00	228250	m	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.15	MT <b>Overburden</b>						
0.00	15.00	Chl; Sil; Oxy <b>Chloritisation; Silicification; Oxydation</b> redish to greyish syenite local pervasive chloritisation and chloritized porph partially silicified to silicified syenite oxydation x-cutting the syenite						
0.00	15.00	Py02; Cp0.1 <b>Pyrite 02%; Chalcopyrite 0.1%</b> 1-2% diss py up to 5% locally in silicified segments at 1.3m and at 12m 3-5% chalcopyrite amalgamated on qtz-carb veins						
0.15	0.45	MT; I2D <b>Casing; Syenite</b> altered oxydized pinkish syenite  recuperated from casing, all sent to lab	0.15	0.45	228257	0.30	0.272	0.272
0.45	15.00	SY <b>Syenite</b> greyish-redish syenite locally porphyric : fds porph mostly 5mm. locally mottled partially silicified segments. 3% qtz-carb veins 0.5% milky qtz-carb veins from 2-5% diss py in grey partially silicified segments oxydized and altered segments x-cutting the syenite	0.45	1.50	228258	1.05	0.069	0.069
			1.50	3.00	228259	1.50	0.007	0.007
			3.00	4.50	228261	1.50	0.020	0.020
			4.50	6.00	228262	1.50	0.009	0.009
			6.00	7.50	228263	1.50	0.006	0.006
			7.50	9.00	228264	1.50	0.009	0.009
			9.00	10.50	228265	1.50	0.008	0.008
			10.50	12.00	228266	1.50	0.008	0.008
			12.00	13.50	228267	1.50	0.459	0.459
			13.50	15.00	228269	1.50	0.217	0.217
15.00	<b>Fin du sondage</b> Nombre d'échantillons : 11 Nombre d'échantillons QAQC : 2 Longueur totale échantillonnée : 14,85							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
1.50	3.00	228260	O61d	1.50	4.890	4.910
12.00	13.50	228268	m	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :** B09-99A

Titre minier : CM 292

Section :

Canton : Duparquet

Niveau : Surface

Rang :

Place de travail : Beattie mine site

Foré par : Foramex

Lot :

Décrit par : Carl Corriveau

Du : 2009-12-06

Date de description : 2009-12-11

Au : 2009-12-10

Collet

UTM

Azimut : 179.12°

Plongée : -44.90°

Longueur : 213.00 m

Est 631 058.0

Nord 5 374 445.2

Élévation 309.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	15.00	180.00°	-45.00°	Non
Reflex	18.00	175.80°	-45.30°	Oui
Reflex	21.00	184.70°	-45.30°	Oui
Reflex	24.00	180.60°	-45.10°	Non
Reflex	27.00	181.40°	-45.10°	Non
Reflex	30.00	180.70°	-45.30°	Non
Reflex	33.00	182.80°	-45.20°	Non
Reflex	36.00	183.00°	-45.20°	Non
Reflex	39.00	182.80°	-45.20°	Non
Reflex	42.00	183.70°	-45.40°	Non
Reflex	45.00	183.70°	-45.40°	Non
Reflex	48.00	183.60°	-45.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	51.00	182.40°	-45.60°	Non
Reflex	54.00	183.10°	-45.60°	Non
Reflex	57.00	182.40°	-45.60°	Non
Reflex	60.00	183.60°	-45.50°	Non
Reflex	63.00	183.70°	-45.50°	Non
Reflex	66.00	182.90°	-45.70°	Non
Reflex	69.00	184.00°	-45.60°	Non
Reflex	72.00	184.40°	-45.60°	Non
Reflex	75.00	183.80°	-45.70°	Non
Reflex	78.00	184.90°	-45.60°	Non
Reflex	81.00	183.50°	-45.60°	Non
Reflex	84.00	183.60°	-45.50°	Non

Description

GPS Datum NAD83, UTM Zone 17.

all downholes survey corrected for magnetic declinaison -12.5W

Dimension de la carotte : NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT <b>Overburden</b>						
0.00	17.80	Py0.5 <b>Pyrite 0.5%</b> Traces disseminated Py						
3.00	19.70	SY; POR <b>Syenite; Porphyric</b> Redish grey to greenish porphyritic syenite. Fine grain matrix. 5-8% 5mm and more feldspars porphyries.  4% white Qz-carb veins.  17.8m- 19.7m Partially silicified, leached and aphanitic grey segments. 2-3% Blackish Py veinlets	3.00	4.50	226507	1.50	0.043	0.043
			4.50	6.00	226508	1.50	0.011	0.011
			6.00	7.50	226509	1.50	0.010	0.010
			7.50	9.00	226511	1.50	0.008	0.008
			9.00	10.50	226512	1.50	0.011	0.011
			10.50	12.00	226513	1.50	0.016	0.016
			12.00	13.50	226514	1.50	0.009	0.009
			13.50	15.00	226515	1.50	0.007	0.007
			15.00	16.50	226516	1.50	<0.005	0.001
			16.50	18.00	226517	1.50	0.057	0.057
3.00	17.80	Oxy <b>Oxydation</b> Oxydized rusty fractures. Weak chlorite						
17.80	19.70	Sil <b>Silicification</b> Strongly silicified and leached segments obliterating primary texture.						
17.80	19.70	Py02; Cp <b>Pyrite 02%; Chalcopyrite</b> 5cm Qz-carb veins at upper contact. Drusy Qz cavities. traces Cp 2-3% Blackish Py veinlets	18.00	19.50	226518	1.50	0.046	0.046
			19.50	21.00	226519	1.50	0.037	0.037
19.70	32.50	SY; MNZD; POR; BR <b>Syenite; Mineralized; Porphyric; Brecciated</b> Redish grey to green mineralized porphyritic syenite with brecciated segment  (28.05m- 29.4m) Mineralized Breccia. 5-8% Py diss and veinlets  Medium grey to dark grey partially silicified and mineralized segments						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
19.70	32.50	<p>crosscutting redish porphyritic syenite. 5%Py disseminated and veinlets</p> <p>4% blackish Py veinlets.</p> <p>5% white silica-Qz (+-Py) veins and veinlets sometimes breccia veins.</p> <p>Sil</p> <p><b>Silicification</b> Partially silicified. minor sericite hairline veinlets and altered porphyries.</p>							
19.70	32.50	<p>Py05</p> <p><b>Pyrite 05%</b> (28.05m- 29.4m) Mineralized Breccia. 5-8% Py diss and veinlets</p> <p>Medium grey to dark grey partially silicified and mineralized segments crosscutting redish porphyritic syenite. 5%Py disseminated and veinlets</p> <p>4% blackish Py veinlets.</p> <p>5% white silica-Qz (+-Py) veins and veinlets.</p>	21.00	22.50	226520	1.50	0.009		0.009
			22.50	24.00	226521	1.50	0.080		0.080
			24.00	25.50	226522	1.50	0.125		0.125
			25.50	27.00	226523	1.50	0.073		0.073
			27.00	28.50	226524	1.50	0.160		0.160
			28.50	30.00	226525	1.50	0.175		0.175
			30.00	31.50	226526	1.50	1.585		1.585
			31.50	33.00	226527	1.50	0.540		0.540
32.50	76.10	<p>SY; POR; MNZD</p> <p><b>Syenite; Porphyric; Mineralized</b> Redish porphyritic syenite crosscut by medium grey to dark grey partially silicified and mineralized segments, veins and brecciated segments. 5%Py disseminated and veinlets in partially silicified segments and veins. 2% blackish pirite veinlets. 3% Qz-Carb veins/veinlets.</p>							
32.50	76.10	<p>Ser</p> <p><b>Sericitisation</b> Moderate pervasive sericitisation, veinlets and replacing porphyries. Locally patially silicified segments and silica veins</p> <p>Week chloritisation</p>							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
32.50	76.10	Py02 <b>Pyrite 02%</b> Overall 2% Py disseminated.  Locally: 5%Py in partially silicified segments and brecciated segments (39.6m-40m) 2% blackish Py veinlets.	33.00	34.50	226528	1.50	0.054		0.054
			34.50	36.00	226529	1.50	0.052		0.052
			36.00	37.50	226531	1.50	0.858		0.858
			37.50	39.00	226532	1.50	0.260		0.260
			39.00	40.50	226533	1.50	0.126		0.126
39.60	40.00	BX <b>Breccia</b> Matrix supported hydrolic breccia. Chloritized, sericitized and partially silicified matrix. heterogenous subangular clasts: qz (vn), qz-Carb (vn), black chl fragments. All size fragments up to 3cm. 3% fine disseminated Py in matrix and veinlets.	40.50	42.00	226534	1.50	0.081		0.081
			42.00	43.50	226535	1.50	0.034		0.034
			43.50	45.00	226536	1.50	0.062		0.062
			45.00	46.50	226537	1.50	0.006		0.006
			46.50	48.00	226538	1.50	0.027		0.027
50.00	50.20	FOL <b>Foliation 45°</b> Rusty chloritized and sericitized foliated segment. 40-45TCA	48.00	49.50	226539	1.50	0.006		0.006
			49.50	51.00	226541	1.50	0.010		0.010
			51.00	52.50	226542	1.50	0.035		0.035
			52.50	54.00	226543	1.50	0.049		0.049
			54.00	55.50	226544	1.50	0.152		0.152
			55.50	57.00	226545	1.50	0.117		0.117
			57.00	58.50	226546	1.50	0.197		0.197
			58.50	60.00	226547	1.50	0.117		0.117
			60.00	61.50	226548	1.50	0.160		0.160
			61.50	63.00	226549	1.50	0.197		0.197
			63.00	64.50	226551	1.50	0.165		0.165
			64.50	66.00	226552	1.50	0.624		0.624
			66.00	67.50	226553	1.50	0.012		0.012
67.50	69.00	226554	1.50	0.012		0.012			
69.00	70.50	226555	1.50	0.636		0.636			
70.50	72.00	226556	1.50	0.447		0.447			
72.00	73.50	226557	1.50	0.171		0.171			
73.50	75.00	226558	1.50	0.065		0.065			
75.00	76.50	226559	1.50	0.101		0.101			
76.10	81.20	SY; MNZD <b>Syenite; Mineralized</b>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Rusty and sericitized upper contact. Porphyritic to brecciated dark purple to green Mineralized syenite. Partially silicified. Partially to totally sericitized feldspars porphyries. Green sericitized patches. 4% disseminated Py in dark purple grey partially silicified segments. 2% Qz-carb veinlets.  TRansitional lower contact.							
76.10	81.20	Ser; Sil	76.50	78.00	226560	1.50	1.580		1.580
		<b>Sericitisation; Silicification</b>	78.00	79.50	226561	1.50	0.843		0.843
		Partially silicified dark purple segments.	79.50	81.00	226562	1.50	0.436		0.436
		Partially to totally sericitized feldspars porphyries and Green pervasive sericitized patches.	81.00	82.50	226563	1.50	0.068		0.068
76.10	81.10	Py04 <b>Pyrite 04%</b>							
		Fine disseminated Py 4% essentially in drak purple silicified segments.							
81.10	111.00	Py02 <b>Pyrite 02%</b>							
		Dark to medium purple syenite segments mineralized. 2-5% very fine disseminated Py.							
81.20	111.00	SY; POR; MNZD <b>Syenite; Porphyric; Mineralized</b>							
		Redish to purple to green porphyritic syenite. Dark to medium purple syenite is mineralized. 2% very fine disseminated Py. Greenish sericitized segments . 5-10% 5mm and more feldspars porphyries. Partially sericitized and albitized feldspars porphyries.  7-10% white to pinkish Qz-carbonates veins all directions and sometimes brecciating the syenite.							
81.20	111.00	Ser; Sil	82.50	84.00	226564	1.50	0.137		0.137
		<b>Sericitisation; Silicification</b>	84.00	85.50	226565	1.50	0.064		0.064
		Greenish sericitized segments .	85.50	87.00	226566	1.50	0.159		0.159
		Partially silicified purple segments	87.00	88.50	226567	1.50	0.061		0.061
			88.50	90.00	226568	1.50	0.122		0.122
			90.00	91.50	226569	1.50	0.310		0.310

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			91.50	93.00	226571	1.50		0.180		0.180
			93.00	94.50	226572	1.50		0.029		0.029
			94.50	96.00	226573	1.50		0.081		0.081
			96.00	97.50	226574	1.50		0.187		0.187
			97.50	99.00	226575	1.50		0.074		0.074
			99.00	100.50	226576	1.50		0.085		0.085
			100.50	102.00	226577	1.50		0.207		0.207
			102.00	103.50	226578	1.50		0.083		0.083
			103.50	105.00	226579	1.50		0.075		0.075
			105.00	106.50	226581	1.50		0.030		0.030
			106.50	108.00	226582	1.50		0.141		0.141
			108.00	109.50	226583	1.50		0.056		0.056
109.50	110.30	FOL <b>Foliation 65°</b> Very altered green foliated segments. Strong sericite and chlorite pervasive alteration. 60-75 TCA. Small plicated deformation associated with foliation.	109.50	111.00	226584	1.50		0.013		0.013
111.00	182.30	SY; POR <b>Syenite; Porphyric</b> Redish green porphyritic syenite.  5% 5mm and more feldspars porphyries partially sericitized. 3% Qz-Carb (Hm Py) veins. 1% chlorite fractures and veins. 5-8% green white sericite and carbonates veinlets spider web texture. 2% Hematite granulars masses and veins  locally brecciated								
111.00	182.30	Ser <b>Sericitisation</b> 5-8% pervasive green sericite veinlets spider web texture.								
111.00	182.30	Py; Hm; Cp <b>Pyrite ; Hematite ; Chalcopyrite</b> Traces to 1% fine grain disseminated Py 2% Hematite granulars masses veins	111.00	112.50	226585	1.50		0.011		0.011
			112.50	114.00	226586	1.50		0.015		0.015

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Traces Cp								
124.6m-127.4m: Partially silicified segment. 8% Hematite granular masses and veins. 3-5% Py disseminated.								
152.3m- 153m: Grey Partially Si segment. 3-5% diss and stringers Py, 2% granular masses Hematite and veins								
166.2m-166.55m: Breccia segments. Silica-sericite-carbonate matrix. 3% Py								
113.40	113.50	VEI;3;QzCb;T;30°;Py05;	114.00	115.50	226587	1.50	<0.005	0.001
<b>Vein 3 Quartz Carbonate Tension 30° Pyrite05%</b>								
		3cm Qz-carb: Saccaroidale fine grain qz. 30TCA. Fine granular Py masses.	115.50	117.00	226588	1.50	0.006	0.006
			117.00	118.50	226589	1.50	0.064	0.064
117.70	118.10	VEI;40;QzCb;T;30°;Py03Cp01;	118.50	120.00	226591	1.50	0.005	0.005
<b>Vein 40 Quartz Carbonate Tension 30° Pyrite03%</b>								
<b>Chalcopyrite01%</b>								
40 cm white pink Qz-Carb veins. Geode or cavities filled with Drusy qz, Calcite, Gypsum, Py, Chalcopyrite.								
			120.00	121.50	226592	1.50	0.005	0.005
			121.50	123.00	226593	1.50	0.011	0.011
			123.00	124.50	226594	1.50	0.026	0.026
			124.50	126.00	226595	1.50	4.110	4.04
			126.00	127.50	226596	1.50	5.450	5.78
			127.50	129.00	226597	1.50	5.110	5.58
			129.00	130.50	226598	1.50	0.013	0.013
			130.50	132.00	226599	1.50	0.015	0.015
			132.00	133.50	226600	1.50	0.013	0.013
			133.50	135.00	226601	1.50	0.023	0.023
			135.00	136.50	226602	1.50	0.034	0.034
			136.50	138.00	226603	1.50	0.044	0.044
			138.00	139.50	226604	1.50	0.006	0.006
			139.50	141.00	226605	1.50	0.009	0.009
			141.00	142.50	226606	1.50	0.045	0.045
			142.50	144.00	226607	1.50	0.031	0.031
			144.00	145.50	226608	1.50	0.035	0.035
			145.50	147.00	226609	1.50	0.069	0.069
			147.00	148.50	226611	1.50	0.225	0.225
			148.50	150.00	226612	1.50	0.093	0.093

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			150.00	151.50	226613	1.50		0.156		0.156
			151.50	153.00	226614	1.50		0.809		0.809
			153.00	154.50	226615	1.50		0.067		0.067
			154.50	156.00	226616	1.50		0.142		0.142
			156.00	157.50	226617	1.50		0.114		0.114
			157.50	159.00	226618	1.50		0.119		0.119
			159.00	160.50	226619	1.50		0.061		0.061
			160.50	162.00	226620	1.50		0.120		0.120
			162.00	163.50	226621	1.50		0.085		0.085
			163.50	165.00	226622	1.50		0.117		0.117
			165.00	166.50	226623	1.50		0.212		0.212
			166.50	168.00	226624	1.50		0.230		0.230
			168.00	169.50	226625	1.50		0.013		0.013
			169.50	171.00	226626	1.50		0.034		0.034
			171.00	172.50	226627	1.50		0.609		0.609
			172.50	174.00	226628	1.50		0.873		0.873
			174.00	175.50	226629	1.50		0.011		0.011
			175.50	177.00	226631	1.50		0.075		0.075
			177.00	178.50	226632	1.50		0.102		0.102
			178.50	180.00	226633	1.50		0.085		0.085
			180.00	181.50	226634	1.50		0.068		0.068
			181.50	183.00	226635	1.50		0.288		0.288
182.30	209.20	SY; FIN <b>Syenite; Fine grains</b> Fine grains to aphanitic very altered redish green syenite. Partially silicified grey segments. Strongly leached and sericitized green segments. 2% white pink Qz-carb veins 2% chlorite veins and veinlets								
182.30	209.20	Ser; Sil <b>Sericitisation; Silicification</b> Strongly leached and sericitized green segments. Partially silicified grey segments.								
182.30	209.20	Py <b>Pyrite</b> Traces diss Py. Generally not min.	183.00	184.50	226636	1.50		0.360		0.360
			184.50	186.00	226637	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			186.00	187.50	226638	1.50	0.204		0.204
			187.50	189.00	226639	1.50	0.080		0.080
			189.00	190.50	226641	1.50	<0.005		0.001
			190.50	192.00	226642	1.50	<0.005		0.001
			192.00	193.50	226643	1.50	<0.005		0.001
			193.50	195.00	226644	1.50	<0.005		0.001
			195.00	196.50	226645	1.50	<0.005		0.001
			196.50	198.00	226646	1.50	<0.005		0.001
			198.00	199.50	226647	1.50	0.017		0.017
			199.50	201.00	226648	1.50	0.084		0.084
			201.00	202.50	226649	1.50	0.007		0.007
			202.50	204.00	226651	1.50	0.070		0.070
			204.00	205.50	226652	1.50	0.009		0.009
			205.50	207.00	226653	1.50	0.006		0.006
			207.00	208.50	226654	1.50	0.148		0.148
			208.50	210.00	226655	1.50	0.843		0.843
209.20	213.00	SY; POR <b>Syenite; Porphyric</b> Redish porphyritic syenite.  5-10% feldspars porphyries partially chloritized.  EOH : 213m							
209.20	213.00	Chl; Ser <b>Chloritisation; Sericitisation</b> Week chlorite veinlets and partially altered porphyries.  Moderate sericitisation partially altering porphyries and veinlets.							
209.20	213.00	Py01 <b>Pyrite 01%</b> Traces to 1% Py  3-5% disseminated Py in partially silicified segments (209m.2-211.3m).	210.00	211.50	226656	1.50	0.099		0.099
			211.50	213.00	226657	1.50	0.008		0.008

# Corporation Minière Osisko Div. Exploration

213.00

Fin du sondage

Nombre d'échantillons : 140

Nombre d'échantillons QAQC : 11

Longueur totale échantillonnée : 210.00

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	7.50	226510	O50Pb	1.50	0.859	0.859
34.50	36.00	226530	O6Pc	1.50	1.540	1.540
48.00	49.50	226540	m	1.50	<0.005	0.001
61.50	63.00	226550	O61d	1.50	4.810	4.830
90.00	91.50	226570	O50Pb	1.50	0.865	0.865
103.50	105.00	226580	m	1.50	<0.005	0.001
117.00	118.50	226590	O54Pa	1.50	2.940	2.940
145.50	147.00	226610	O50Pb	1.50	0.808	0.808
174.00	175.50	226630	O6Pc	1.50	1.585	1.585
187.50	189.00	226640	m	1.50	<0.005	0.001
201.00	202.50	226650	O54Pa	1.50	2.870	2.870



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-111**

Titre minier :

Section :                      631300

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              malartic

Décrit par :              Guy.Gbaguidi

Lot :

Du :                      2010-02-16

Date de description :

Au :                      2010-02-19

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -61.00°  
 Longueur :                      229.00 m

Est	631 296.1
Nord	5 374 457.1
Élévation	288.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	348.90°	-60.10°	Oui
Reflex	5.00	348.90°	-60.10°	Oui
Reflex	8.00	0.20°	-59.90°	Non
Reflex	11.00	0.20°	-59.80°	Non
Reflex	14.00	359.90°	-59.80°	Non
Reflex	17.00	0.10°	-59.80°	Non
Reflex	20.00	0.00°	-59.70°	Non
Reflex	23.00	359.80°	-59.70°	Non
Reflex	26.00	0.30°	-59.60°	Non
Reflex	29.00	0.60°	-59.50°	Non
Reflex	32.00	359.80°	-59.40°	Non
Reflex	35.00	0.00°	-59.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.10°	-59.40°	Oui
Reflex	41.00	0.80°	-59.40°	Non
Reflex	44.00	2.30°	-59.40°	Non
Reflex	47.00	1.80°	-59.40°	Non
Reflex	50.00	1.60°	-59.40°	Non
Reflex	53.00	1.40°	-59.30°	Non
Reflex	56.00	1.50°	-59.30°	Non
Reflex	59.00	1.40°	-59.30°	Non
Reflex	62.00	0.30°	-59.30°	Non
Reflex	65.00	359.60°	-59.30°	Non
Reflex	68.00	0.90°	-59.30°	Non
Reflex	71.00	1.00°	-59.20°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.40°	-59.10°	Non	Reflex	173.00	359.90°	-58.20°	Non
Reflex	77.00	2.00°	-59.00°	Non	Reflex	176.00	1.50°	-58.20°	Non
Reflex	80.00	2.10°	-59.00°	Non	Reflex	179.00	2.50°	-58.20°	Non
Reflex	83.00	1.50°	-58.90°	Non	Reflex	182.00	3.30°	-58.20°	Non
Reflex	86.00	1.30°	-58.90°	Non	Reflex	185.00	1.80°	-58.20°	Non
Reflex	89.00	1.10°	-58.80°	Non	Reflex	188.00	2.00°	-58.20°	Non
Reflex	92.00	0.70°	-58.70°	Oui	Reflex	191.00	1.90°	-58.20°	Non
Reflex	95.00	1.80°	-58.70°	Non	Reflex	194.00	357.80°	-58.20°	Non
Reflex	98.00	1.20°	-58.60°	Non	Reflex	197.00	359.20°	-58.20°	Non
Reflex	101.00	1.40°	-58.60°	Non	Reflex	200.00	2.50°	-58.10°	Non
Reflex	104.00	1.40°	-58.50°	Non	Reflex	203.00	3.40°	-58.10°	Non
Reflex	107.00	1.90°	-58.50°	Non	Reflex	206.00	3.80°	-58.10°	Non
Reflex	110.00	3.20°	-58.50°	Non	Reflex	209.00	3.70°	-58.10°	Non
Reflex	113.00	3.70°	-58.50°	Non	Reflex	212.00	3.70°	-58.00°	Non
Reflex	116.00	3.60°	-58.50°	Non	Reflex	215.00	3.50°	-58.00°	Non
Reflex	119.00	3.30°	-58.50°	Non	Reflex	218.00	4.10°	-57.90°	Non
Reflex	122.00	2.80°	-58.40°	Non	Reflex	221.00	5.70°	-57.90°	Non
Reflex	125.00	4.80°	-58.40°	Oui	Reflex	224.00	2.80°	-58.00°	Oui
Reflex	128.00	1.50°	-58.40°	Non					
Reflex	131.00	1.20°	-58.40°	Non					
Reflex	134.00	1.00°	-58.40°	Non					
Reflex	137.00	3.30°	-58.40°	Non					
Reflex	140.00	3.60°	-58.40°	Non					
Reflex	143.00	1.60°	-58.30°	Non					
Reflex	146.00	2.50°	-58.40°	Non					
Reflex	149.00	2.90°	-58.30°	Non					
Reflex	152.00	1.70°	-58.30°	Non					
Reflex	155.00	0.90°	-58.30°	Non					
Reflex	158.00	0.30°	-58.30°	Non					
Reflex	161.00	3.30°	-58.20°	Non					
Reflex	164.00	4.30°	-58.20°	Oui					
Reflex	167.00	2.90°	-58.20°	Non					
Reflex	170.00	2.80°	-58.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.90	MT Mort-terrain MT						
5.90	229.00	SY Syénite Syénite	5.90	7.50	144097	1.60	0.124	0.124
			7.50	9.00	144098	1.50	0.073	0.073
			9.00	10.50	144099	1.50	0.074	0.074
			10.50	12.00	144100	1.50	0.399	0.399
			12.00	13.50	144101	1.50	0.502	0.502
			13.50	15.00	144102	1.50	0.534	0.534
			15.00	16.30	144103	1.30	1.170	1.170
			16.30	18.00	144104	1.70	0.220	0.220
			18.00	19.00	144105	1.00	0.089	0.089
			19.00	20.10	144106	1.10	6.300	6.300
			20.10	21.50	144107	1.40	0.018	0.018
			21.50	23.00	144108	1.50	0.181	0.181
			23.00	24.60	144109	1.60	0.087	0.087
			24.60	26.00	144110	1.40	0.271	0.271
			26.00	27.30	144111	1.30	0.039	0.039
			27.30	28.30	144112	1.00	0.227	0.227
			28.30	29.40	144113	1.10	0.567	0.567
			29.40	31.00	144114	1.60	0.046	0.046
			31.00	32.00	144116	1.00	0.069	0.069
			32.00	33.10	144117	1.10	<0.005	0.001
			33.10	34.40	144119	1.30	0.025	0.025
			34.40	35.40	144120	1.00	0.006	0.006
			35.40	36.40	144121	1.00	0.052	0.052
			36.40	38.00	144122	1.60	0.245	0.245
			38.00	39.50	144123	1.50	<0.005	0.001
			39.50	40.80	144124	1.30	0.044	0.044
			40.80	41.90	144125	1.10	0.010	0.010
			41.90	43.50	144126	1.60	0.232	0.232
			43.50	45.00	144127	1.50	0.006	0.006
			45.00	46.50	144128	1.50	0.005	0.005
			46.50	48.00	144129	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.00	49.50	144130	1.50	0.007		0.007
	49.50	51.00	144131	1.50	<0.005		0.001
	51.00	52.00	144132	1.00	0.054		0.054
	52.00	53.30	144133	1.30	<0.005		0.001
	53.30	54.40	144134	1.10	0.116		0.116
	54.40	56.00	144136	1.60	<0.005		0.001
	56.00	57.50	144137	1.50	0.011		0.011
	57.50	59.00	144139	1.50	0.010		0.010
	59.00	60.50	144140	1.50	<0.005		0.001
	60.50	62.00	144141	1.50	0.256		0.256
	62.00	63.00	144142	1.00	<0.005		0.001
	63.00	64.30	144143	1.30	0.122		0.122
	64.30	65.30	144144	1.00	0.030		0.030
	65.30	67.00	144145	1.70	0.037		0.037
	67.00	68.50	144146	1.50	0.008		0.008
	68.50	70.00	144147	1.50	0.007		0.007
	70.00	71.50	144148	1.50	<0.005		0.001
	71.50	72.70	144149	1.20	0.028		0.028
	72.70	74.00	144150	1.30	0.166		0.166
	74.00	75.60	144151	1.60	0.161		0.161
	75.60	77.00	144152	1.40	0.230		0.230
	77.00	78.50	144153	1.50	0.363		0.363
	78.50	80.00	144154	1.50	<0.005		0.001
	80.00	81.50	144156	1.50	<0.005		0.001
	81.50	83.00	144157	1.50	<0.005		0.001
	83.00	84.50	144159	1.50	<0.005		0.001
	84.50	86.00	144160	1.50	<0.005		0.001
	86.00	87.00	144161	1.00	<0.005		0.001
	87.00	88.50	144162	1.50	<0.005		0.001
	88.50	90.00	144163	1.50	0.011		0.011
	90.00	91.00	144164	1.00	0.014		0.014
	91.00	92.50	144165	1.50	0.052		0.052
	92.50	94.00	144166	1.50	0.041		0.041

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	94.00	95.00	144167	1.00	0.010		0.010
	95.00	96.00	144168	1.00	<0.005		0.001
	96.00	97.50	144169	1.50	0.018		0.018
	97.50	99.00	144170	1.50	0.185		0.185
	99.00	100.00	144171	1.00	0.016		0.016
	100.00	101.20	144172	1.20	<0.005		0.001
	101.20	102.50	144173	1.30	0.036		0.036
	102.50	104.00	144174	1.50	0.243		0.243
	104.00	105.50	144176	1.50	0.112		0.112
	105.50	107.00	144177	1.50	0.009		0.009
	107.00	108.50	144179	1.50	0.550		0.550
	108.50	110.00	144180	1.50	<0.005		0.001
	110.00	111.50	144181	1.50	<0.005		0.001
	111.50	113.00	144182	1.50	<0.005		0.001
	113.00	114.20	144183	1.20	<0.005		0.001
	114.20	115.70	144184	1.50	0.009		0.009
	115.70	117.00	144185	1.30	<0.005		0.001
	117.00	118.00	144186	1.00	0.029		0.029
	118.00	119.40	144187	1.40	<0.005		0.001
	119.40	120.40	144188	1.00	<0.005		0.001
	120.40	121.70	144189	1.30	<0.005		0.001
	121.70	123.00	144190	1.30	<0.005		0.001
	123.00	124.50	144191	1.50	<0.005		0.001
	124.50	126.00	144192	1.50	0.005		0.005
	126.00	127.50	144193	1.50	<0.005		0.001
	127.50	129.00	144194	1.50	<0.005		0.001
	129.00	130.50	144196	1.50	<0.005		0.001
	130.50	132.00	144197	1.50	<0.005		0.001
	132.00	133.50	144199	1.50	<0.005		0.001
	133.50	135.00	144200	1.50	<0.005		0.001
	135.00	136.50	144201	1.50	<0.005		0.001
	136.50	138.00	144202	1.50	<0.005		0.001
	138.00	139.50	144203	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	139.50	141.00	144204	1.50	<0.005		0.001
	141.00	142.50	144205	1.50	<0.005		0.001
	142.50	144.00	144206	1.50	<0.005		0.001
	144.00	145.50	144207	1.50	<0.005		0.001
	145.50	147.00	144208	1.50	<0.005		0.001
	147.00	148.50	144209	1.50	0.007		0.007
	148.50	150.00	144210	1.50	<0.005		0.001
	150.00	151.50	144211	1.50	<0.005		0.001
	151.50	152.50	144212	1.00	<0.005		0.001
	152.50	154.00	144213	1.50	<0.005		0.001
	154.00	155.00	144214	1.00	0.006		0.006
	155.00	156.50	144216	1.50	0.016		0.016
	156.50	158.00	144217	1.50	<0.005		0.001
	158.00	159.30	144219	1.30	0.005		0.005
	159.30	161.00	144220	1.70	<0.005		0.001
	161.00	162.50	144221	1.50	0.053		0.053
	162.50	164.00	144222	1.50	0.127		0.127
	164.00	165.50	144223	1.50	0.104		0.104
	165.50	167.00	144224	1.50	0.022		0.022
	167.00	168.50	144225	1.50	0.028		0.028
	168.50	170.00	144226	1.50	0.121		0.121
	170.00	171.50	144227	1.50	0.017		0.017
	171.50	173.00	144228	1.50	0.163		0.163
	173.00	174.50	144229	1.50	0.024		0.024
	174.50	176.00	144230	1.50	0.005		0.005
	176.00	177.50	144231	1.50	<0.005		0.001
	177.50	179.00	144232	1.50	0.099		0.099
	179.00	180.00	144233	1.00	0.153		0.153
	180.00	181.50	144234	1.50	<0.005		0.001
	181.50	183.00	144236	1.50	0.067		0.067
	183.00	184.50	144237	1.50	0.224		0.224
	184.50	186.00	144239	1.50	0.030		0.030
	186.00	187.50	144240	1.50	0.179		0.179

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	187.50	189.00	144241	1.50	0.023		0.023
	189.00	190.50	144242	1.50	<0.005		0.001
	190.50	192.00	144243	1.50	<0.005		0.001
	192.00	193.40	144244	1.40	0.200		0.200
	193.40	194.40	144245	1.00	0.236		0.236
	194.40	196.00	144246	1.60	0.015		0.015
	196.00	197.40	144247	1.40	0.110		0.110
	197.40	199.00	144248	1.60	0.132		0.132
	199.00	200.50	144249	1.50	4.230		4.230
	200.50	202.00	144250	1.50	1.150		1.150
	202.00	203.50	144251	1.50	0.029		0.029
	203.50	205.00	144252	1.50	0.364		0.364
	205.00	206.50	144253	1.50	0.164		0.164
	206.50	208.00	144254	1.50	0.023		0.023
	208.00	209.50	144256	1.50	0.064		0.064
	209.50	211.00	144257	1.50	0.233		0.233
	211.00	212.50	144259	1.50	0.122		0.122
	212.50	214.00	144260	1.50	<0.005		0.001
	214.00	215.50	144261	1.50	0.033		0.033
	215.50	217.00	144262	1.50	0.055		0.055
	217.00	218.50	144263	1.50	0.025		0.025
	218.50	219.50	144264	1.00	0.151		0.151
	219.50	220.50	144265	1.00	0.418		0.418
	220.50	221.50	144266	1.00	0.222		0.222
	221.50	223.00	144267	1.50	0.171		0.171
	223.00	224.50	144268	1.50	0.092		0.092
	224.50	226.00	144269	1.50	0.142		0.142
	226.00	227.50	144270	1.50	0.217		0.217
	227.50	229.00	144271	1.50	1.460		1.460
229.00	Fin du sondage Nombre d'échantillons : 159 Nombre d'échantillons QAQC : 16 Longueur totale échantillonnée : 223.10						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
29.40	31.00	144115	A3	1.60	0.441	0.441
32.00	33.10	144118	144117	1.10	0.008	0.008
53.30	54.40	144135	B4	1.10	2.590	2.590
56.00	57.50	144138	144137	1.50	<0.005	0.001
78.50	80.00	144155	M1	1.50	<0.005	0.001
81.50	83.00	144158	144157	1.50	0.006	0.006
102.50	104.00	144175	C3	1.50	1.335	1.335
105.50	107.00	144178	144177	1.50	0.010	0.010
127.50	129.00	144195	D2	1.50	0.810	0.810
130.50	132.00	144198	144197	1.50	<0.005	0.001
154.00	155.00	144215	M1	1.00	<0.005	0.001
156.50	158.00	144218	144217	1.50	<0.005	0.001
180.00	181.50	144235	G2	1.50	3.890	3.890
183.00	184.50	144238	144237	1.50	0.316	0.316
206.50	208.00	144255	H	1.50	0.975	0.975
209.50	211.00	144258	144257	1.50	0.161	0.161





Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	78.00	190.80°	-60.10°	Non	Reflex	177.00	192.60°	-60.00°	Non
Reflex	81.00	190.80°	-60.10°	Non	Reflex	180.00	192.50°	-59.90°	Non
Reflex	84.00	191.60°	-60.10°	Non	Reflex	183.00	192.70°	-59.90°	Non
Reflex	87.00	191.00°	-60.10°	Non	Reflex	186.00	192.50°	-60.00°	Non
Reflex	90.00	191.80°	-60.10°	Non	Reflex	189.00	192.40°	-60.00°	Non
Reflex	93.00	191.80°	-60.00°	Non	Reflex	192.00	192.70°	-59.90°	Non
Reflex	96.00	191.10°	-60.00°	Non	Reflex	195.00	192.60°	-59.90°	Non
Reflex	99.00	191.30°	-60.10°	Non	Reflex	198.00	192.80°	-59.90°	Non
Reflex	102.00	190.30°	-60.10°	Non	Reflex	201.00	192.70°	-59.90°	Non
Reflex	105.00	190.60°	-60.10°	Non	Reflex	204.00	192.60°	-59.90°	Non
Reflex	108.00	190.50°	-60.10°	Non	Reflex	207.00	192.70°	-59.90°	Non
Reflex	111.00	192.40°	-60.10°	Non	Reflex	210.00	192.80°	-59.90°	Non
Reflex	114.00	191.70°	-60.10°	Non	Reflex	213.00	192.50°	-59.90°	Non
Reflex	117.00	190.90°	-60.10°	Non	Reflex	216.00	192.50°	-59.90°	Non
Reflex	120.00	192.40°	-60.00°	Non	Reflex	219.00	192.40°	-59.80°	Non
Reflex	123.00	190.90°	-60.00°	Non	Reflex	222.00	192.70°	-59.90°	Non
Reflex	126.00	192.20°	-60.10°	Non	Reflex	225.00	192.60°	-59.90°	Non
Reflex	129.00	192.50°	-60.10°	Non	Reflex	228.00	193.30°	-59.80°	Non
Reflex	132.00	192.60°	-60.10°	Non	Reflex	231.00	193.30°	-59.80°	Non
Reflex	135.00	191.80°	-60.00°	Non	Reflex	234.00	192.70°	-59.90°	Non
Reflex	138.00	191.20°	-60.00°	Non	Reflex	237.00	192.10°	-59.90°	Non
Reflex	141.00	191.70°	-60.00°	Non	Reflex	240.00	192.60°	-59.90°	Non
Reflex	144.00	192.30°	-60.00°	Non	Reflex	243.00	192.70°	-59.90°	Non
Reflex	147.00	192.80°	-60.00°	Non	Reflex	246.00	192.90°	-59.80°	Non
Reflex	150.00	191.50°	-60.00°	Non	Reflex	249.00	192.20°	-59.80°	Non
Reflex	153.00	191.50°	-60.00°	Non	Reflex	252.00	192.60°	-59.80°	Non
Reflex	156.00	192.40°	-60.00°	Non	Reflex	255.00	193.10°	-59.80°	Non
Reflex	159.00	192.50°	-60.00°	Non	Reflex	258.00	192.90°	-59.80°	Non
Reflex	162.00	192.30°	-60.00°	Non	Reflex	261.00	192.60°	-59.70°	Non
Reflex	165.00	192.60°	-60.00°	Non	Reflex	264.00	192.40°	-59.70°	Non
Reflex	168.00	192.50°	-60.00°	Non	Reflex	267.00	192.50°	-59.70°	Non
Reflex	171.00	192.60°	-60.00°	Non	Reflex	270.00	192.60°	-59.70°	Non
Reflex	174.00	192.80°	-60.00°	Non	Reflex	273.00	192.60°	-59.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	276.00	193.10°	-59.60°	Non	Reflex	375.00	193.30°	-59.10°	Non
Reflex	279.00	192.40°	-59.60°	Non	Reflex	378.00	193.20°	-58.90°	Non
Reflex	282.00	192.70°	-59.50°	Non	Reflex	381.00	193.30°	-58.80°	Non
Reflex	285.00	192.30°	-59.60°	Non	Reflex	384.00	192.90°	-58.60°	Non
Reflex	288.00	192.30°	-59.50°	Non	Reflex	387.00	192.90°	-58.40°	Non
Reflex	291.00	192.40°	-59.50°	Non	Reflex	390.00	193.30°	-58.40°	Non
Reflex	294.00	192.10°	-59.50°	Non	Reflex	393.00	193.20°	-58.30°	Non
Reflex	297.00	192.30°	-59.40°	Non	Reflex	396.00	193.30°	-58.30°	Non
Reflex	300.00	191.90°	-59.40°	Non	Reflex	399.00	193.30°	-58.20°	Non
Reflex	303.00	192.30°	-59.40°	Non	Reflex	402.00	192.80°	-58.10°	Non
Reflex	306.00	192.40°	-59.30°	Non	Reflex	405.00	192.90°	-58.10°	Non
Reflex	309.00	193.00°	-59.30°	Non	Reflex	408.00	193.10°	-58.00°	Non
Reflex	312.00	194.10°	-59.30°	Non	Reflex	411.00	193.30°	-58.00°	Non
Reflex	315.00	195.20°	-59.30°	Non	Reflex	414.00	192.50°	-57.90°	Non
Reflex	318.00	194.40°	-59.20°	Non	Reflex	417.00	193.10°	-57.90°	Non
Reflex	321.00	196.10°	-59.30°	Non	Reflex	420.00	192.90°	-57.80°	Non
Reflex	324.00	195.80°	-59.20°	Non	Reflex	423.00	193.30°	-57.80°	Non
Reflex	327.00	195.00°	-59.20°	Non	Reflex	426.00	193.40°	-57.70°	Non
Reflex	330.00	195.80°	-59.20°	Non	Reflex	429.00	193.20°	-57.70°	Non
Reflex	333.00	195.00°	-59.20°	Non	Reflex	432.00	193.40°	-57.60°	Non
Reflex	336.00	194.00°	-59.20°	Non	Reflex	435.00	193.40°	-57.60°	Non
Reflex	339.00	193.50°	-59.20°	Non	Reflex	438.00	193.30°	-57.60°	Non
Reflex	342.00	193.00°	-59.20°	Non	Reflex	441.00	193.60°	-57.60°	Non
Reflex	345.00	193.20°	-59.20°	Non	Reflex	444.00	193.60°	-57.50°	Non
Reflex	348.00	192.30°	-59.20°	Non	Reflex	447.00	193.60°	-57.40°	Non
Reflex	351.00	192.20°	-59.20°	Non	Reflex	450.00	193.70°	-57.40°	Non
Reflex	354.00	192.30°	-59.20°	Non	Reflex	453.00	193.80°	-57.40°	Non
Reflex	357.00	192.60°	-59.20°	Non					
Reflex	360.00	193.00°	-59.20°	Non					
Reflex	363.00	192.90°	-59.20°	Non					
Reflex	366.00	192.30°	-59.20°	Non					
Reflex	369.00	192.30°	-59.20°	Non					
Reflex	372.00	193.10°	-59.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.80	MT Mort-terrain MT						
2.80	371.70	SY Syénite Syénite	2.80	4.00	565795	1.20	0.005	0.005
			4.00	5.50	565796	1.50	0.162	0.162
			5.50	7.00	565797	1.50	0.007	0.007
			7.00	8.50	565798	1.50	0.040	0.040
			8.50	10.00	565799	1.50	0.457	0.457
			10.00	11.50	565800	1.50	1.020	1.020
			11.50	13.00	565801	1.50	0.008	0.008
			13.00	14.50	565802	1.50	<0.005	0.001
			14.50	16.00	565803	1.50	0.446	0.446
			16.00	17.50	565805	1.50	0.067	0.067
			17.50	19.00	565806	1.50	0.068	0.068
			19.00	20.50	565807	1.50	0.301	0.301
			20.50	22.00	565808	1.50	0.057	0.057
			22.00	23.50	565809	1.50	0.048	0.048
			23.50	25.00	565810	1.50	0.804	0.804
			25.00	26.50	565811	1.50	0.161	0.161
			26.50	28.00	565812	1.50	0.249	0.249
			28.00	29.50	565813	1.50	0.361	0.361
			29.50	31.00	565815	1.50	0.101	0.101
			31.00	32.50	565816	1.50	0.077	0.077
			32.50	34.00	565817	1.50	0.009	0.009
			34.00	35.50	565818	1.50	0.148	0.148
			35.50	37.00	565819	1.50	0.076	0.076
			37.00	38.50	565820	1.50	0.037	0.037
			38.50	40.00	565821	1.50	0.063	0.063
			40.00	41.50	565822	1.50	0.043	0.043
			41.50	43.00	565823	1.50	<0.005	0.001
			43.00	44.50	565825	1.50	0.108	0.108
			44.50	46.00	565826	1.50	0.146	0.146
			46.00	47.50	565827	1.50	0.948	0.948
			47.50	49.00	565828	1.50	0.147	0.147

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.00	50.50	565829	1.50	0.028		0.028
	50.50	52.00	565830	1.50	0.033		0.033
	52.00	53.50	565831	1.50	0.053		0.053
	53.50	55.00	565832	1.50	0.225		0.225
	55.00	56.50	565833	1.50	0.005		0.005
	56.50	58.00	565835	1.50	<0.005		0.001
	58.00	59.50	565836	1.50	0.050		0.050
	59.50	61.00	565837	1.50	0.013		0.013
	61.00	62.50	565838	1.50	0.062		0.062
	62.50	64.00	565839	1.50	0.034		0.034
	64.00	65.50	565840	1.50	0.012		0.012
	65.50	67.00	565841	1.50	0.027		0.027
	67.00	68.50	565842	1.50	0.039		0.039
	68.50	70.00	565843	1.50	0.011		0.011
	70.00	71.50	565845	1.50	<0.005		0.001
	71.50	73.00	565846	1.50	0.014		0.014
	73.00	74.50	565847	1.50	0.009		0.009
	74.50	76.00	565848	1.50	0.014		0.014
	76.00	77.50	565849	1.50	0.008		0.008
	77.50	79.00	565850	1.50	<0.005		0.001
	79.00	80.50	565851	1.50	0.005		0.005
	80.50	82.00	565852	1.50	0.006		0.006
	82.00	83.50	565853	1.50	<0.005		0.001
	83.50	85.00	565855	1.50	<0.005		0.001
	85.00	86.50	565856	1.50	0.006		0.006
	86.50	88.00	565857	1.50	<0.005		0.001
	88.00	89.50	565858	1.50	0.007		0.007
	89.50	91.00	565859	1.50	0.480		0.480
	91.00	92.50	565860	1.50	0.456		0.456
	92.50	94.00	565861	1.50	0.773		0.773
	94.00	95.50	565862	1.50	0.758		0.758
	95.50	97.00	565863	1.50	0.020		0.020
	97.00	98.50	565865	1.50	0.601		0.601

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.50	100.00	565866	1.50	0.006		0.006
	100.00	101.50	565867	1.50	0.020		0.020
	101.50	103.00	565868	1.50	0.018		0.018
	103.00	104.50	565869	1.50	0.040		0.040
	104.50	106.00	565870	1.50	0.005		0.005
	106.00	107.50	565871	1.50	0.011		0.011
	107.50	109.00	565872	1.50	0.010		0.010
	109.00	110.50	565873	1.50	<0.005		0.001
	110.50	112.00	565875	1.50	0.009		0.009
	112.00	113.50	565876	1.50	0.025		0.025
	113.50	115.00	565877	1.50	0.019		0.019
	115.00	116.50	565878	1.50	<0.005		0.001
	116.50	118.00	565879	1.50	0.005		0.005
	118.00	119.50	565880	1.50	<0.005		0.001
	119.50	121.00	565881	1.50	<0.005		0.001
	121.00	122.50	565882	1.50	<0.005		0.001
	122.50	124.00	565883	1.50	<0.005		0.001
	124.00	125.50	565885	1.50	<0.005		0.001
	125.50	127.00	565886	1.50	0.006		0.006
	127.00	128.50	565887	1.50	0.009		0.009
	128.50	130.00	565888	1.50	0.099		0.099
	130.00	131.50	565889	1.50	0.994		0.994
	131.50	133.00	565890	1.50	0.476		0.476
	133.00	134.50	565891	1.50	<0.005		0.001
	134.50	136.00	565892	1.50	0.005		0.005
	136.00	137.50	565893	1.50	<0.005		0.001
	137.50	139.00	565895	1.50	0.007		0.007
	139.00	140.50	565896	1.50	0.010		0.010
	140.50	142.00	565897	1.50	0.065		0.065
	142.00	143.50	565898	1.50	0.020		0.020
	143.50	145.00	565899	1.50	0.016		0.016
	145.00	146.50	565900	1.50	0.294		0.294
	146.50	148.00	565901	1.50	0.065		0.065

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.00	149.50	565902	1.50	0.020		0.020
	149.50	151.00	565903	1.50	0.322		0.322
	151.00	152.50	565905	1.50	0.081		0.081
	152.50	154.00	565906	1.50	0.051		0.051
	154.00	155.50	565907	1.50	0.010		0.010
	155.50	157.00	565908	1.50	0.012		0.012
	157.00	158.50	565909	1.50	0.020		0.020
	158.50	160.00	565910	1.50	0.005		0.005
	160.00	161.50	565911	1.50	0.021		0.021
	161.50	163.00	565912	1.50	0.015		0.015
	163.00	164.50	565913	1.50	0.022		0.022
	164.50	166.00	565915	1.50	0.013		0.013
	166.00	167.50	565916	1.50	0.050		0.050
	167.50	168.90	565917	1.40	0.145		0.145
	168.90	170.60	565918	1.70	0.065		0.065
	170.60	172.00	565919	1.40	2.670		2.670
	172.00	173.50	565920	1.50	0.171		0.171
	173.50	175.00	565921	1.50	0.029		0.029
	175.00	176.50	565922	1.50	0.027		0.027
	176.50	178.00	565923	1.50	0.061		0.061
	178.00	179.50	565925	1.50	0.011		0.011
	179.50	181.00	565926	1.50	0.113		0.113
	181.00	182.50	565927	1.50	0.090		0.090
	182.50	184.00	565928	1.50	0.025		0.025
	184.00	185.50	565929	1.50	0.015		0.015
	185.50	187.00	565930	1.50	0.008		0.008
	187.00	188.50	565931	1.50	0.009		0.009
	188.50	190.00	565932	1.50	0.005		0.005
	190.00	191.50	565933	1.50	0.006		0.006
	191.50	193.00	565935	1.50	0.023		0.023
	193.00	194.50	565936	1.50	0.007		0.007
	194.50	196.00	565937	1.50	0.005		0.005
	196.00	197.50	565938	1.50	0.345		0.345

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.50	199.00	565939	1.50	0.020		0.020
	199.00	200.50	565940	1.50	0.024		0.024
	200.50	202.00	565941	1.50	0.019		0.019
	202.00	203.50	565942	1.50	0.025		0.025
	203.50	205.00	565943	1.50	0.009		0.009
	205.00	206.50	565945	1.50	0.087		0.087
	206.50	208.00	565946	1.50	0.026		0.026
	208.00	209.50	565947	1.50	0.028		0.028
	209.50	211.00	565948	1.50	0.015		0.015
	211.00	212.50	565949	1.50	0.009		0.009
	212.50	214.00	565950	1.50	0.008		0.008
	214.00	215.50	565951	1.50	0.038		0.038
	215.50	217.00	565952	1.50	0.133		0.133
	217.00	218.50	565953	1.50	0.079		0.079
	218.50	220.00	565955	1.50	0.169		0.169
	220.00	221.50	565956	1.50	0.021		0.021
	221.50	223.00	565957	1.50	0.023		0.023
	223.00	224.50	565958	1.50	0.008		0.008
	224.50	226.00	565959	1.50	0.053		0.053
	226.00	227.50	565960	1.50	0.075		0.075
	227.50	229.00	565961	1.50	0.148		0.148
	229.00	230.50	565962	1.50	0.017		0.017
	230.50	232.00	565963	1.50	0.015		0.015
	232.00	233.50	565965	1.50	0.010		0.010
	233.50	235.00	565966	1.50	0.027		0.027
	235.00	236.50	565967	1.50	0.053		0.053
	236.50	238.00	565968	1.50	0.158		0.158
	238.00	239.50	565969	1.50	0.102		0.102
	239.50	241.00	565970	1.50	0.010		0.010
	241.00	242.50	565971	1.50	0.053		0.053
	242.50	244.00	565972	1.50	0.020		0.020
	244.00	245.50	565973	1.50	0.010		0.010
	245.50	247.00	565975	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	247.00	248.50	565976	1.50	<0.005		0.001
	248.50	250.00	565977	1.50	0.023		0.023
	250.00	251.50	565978	1.50	<0.005		0.001
	251.50	253.00	565979	1.50	<0.005		0.001
	253.00	254.50	565980	1.50	0.011		0.011
	254.50	256.00	565981	1.50	0.007		0.007
	256.00	257.50	565982	1.50	0.155		0.155
	257.50	259.00	565983	1.50	0.120		0.120
	259.00	260.50	565985	1.50	0.099		0.099
	260.50	262.00	565986	1.50	0.117		0.117
	262.00	263.50	565987	1.50	0.923		0.923
	263.50	265.00	565988	1.50	0.015		0.015
	265.00	266.50	565989	1.50	0.015		0.015
	266.50	268.00	565990	1.50	0.006		0.006
	268.00	269.50	565991	1.50	0.007		0.007
	269.50	271.00	565992	1.50	0.006		0.006
	271.00	272.50	565993	1.50	0.019		0.019
	272.50	274.00	565995	1.50	0.010		0.010
	274.00	275.50	565996	1.50	<0.005		0.001
	275.50	277.00	565997	1.50	0.007		0.007
	277.00	278.50	565998	1.50	0.005		0.005
	278.50	280.00	565999	1.50	<0.005		0.001
	280.00	281.50	566000	1.50	0.006		0.006
	281.50	283.00	566001	1.50	0.051		0.051
	283.00	284.50	566002	1.50	0.204		0.204
	284.50	286.00	566003	1.50	0.010		0.010
	286.00	287.50	566005	1.50	<0.005		0.001
	287.50	289.00	566006	1.50	0.025		0.025
	289.00	290.50	566007	1.50	0.009		0.009
	290.50	292.00	566008	1.50	<0.005		0.001
	292.00	293.50	566009	1.50	0.118		0.118
	293.50	295.00	566010	1.50	0.007		0.007
	295.00	296.50	566011	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.50	298.00	566012	1.50	0.007		0.007
	298.00	299.50	566013	1.50	<0.005		0.001
	299.50	301.00	566015	1.50	0.047		0.047
	301.00	302.00	566016	1.00	0.009		0.009
	302.00	303.50	566017	1.50	0.169		0.169
	303.50	305.00	566018	1.50	0.022		0.022
	305.00	306.50	566019	1.50	0.050		0.050
	306.50	308.00	566020	1.50	0.093		0.093
	308.00	309.40	566021	1.40	0.006		0.006
	309.40	311.00	566022	1.60	0.022		0.022
	311.00	312.50	566023	1.50	<0.005		0.001
	312.50	314.00	566025	1.50	0.026		0.026
	314.00	315.50	566026	1.50	<0.005		0.001
	315.50	317.00	566027	1.50	<0.005		0.001
	317.00	318.50	566028	1.50	<0.005		0.001
	318.50	320.00	566029	1.50	<0.005		0.001
	320.00	321.50	566030	1.50	0.024		0.024
	321.50	323.00	566031	1.50	0.420		0.420
	323.00	324.50	566032	1.50	0.182		0.182
	324.50	326.00	566033	1.50	0.009		0.009
	326.00	327.50	566035	1.50	<0.005		0.001
	327.50	329.00	566036	1.50	0.006		0.006
	329.00	330.50	566037	1.50	0.064		0.064
	330.50	332.00	566038	1.50	<0.005		0.001
	332.00	333.50	566039	1.50	0.017		0.017
	333.50	335.00	566040	1.50	0.044		0.044
	335.00	336.50	566041	1.50	<0.005		0.001
	336.50	338.00	566042	1.50	0.018		0.018
	338.00	339.50	566043	1.50	0.008		0.008
	339.50	341.00	566045	1.50	<0.005		0.001
	341.00	342.50	566046	1.50	<0.005		0.001
	342.50	344.00	566047	1.50	<0.005		0.001
	344.00	345.50	566048	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
371.70      424.60      BA <b>Basalte</b> Basalte	345.50	347.00	566049	1.50	0.035	4.49	0.035
	347.00	348.50	566050	1.50	<0.005		0.001
	348.50	350.00	566051	1.50	0.025		0.025
	350.00	351.50	566052	1.50	<0.005		0.001
	351.50	353.00	566053	1.50	0.005		0.005
	353.00	354.50	566055	1.50	0.010		0.010
	354.50	356.00	566056	1.50	0.010		0.010
	356.00	357.50	566057	1.50	0.011		0.011
	357.50	359.00	566058	1.50	0.021		0.021
	359.00	360.50	566059	1.50	<0.005		0.001
	360.50	362.00	566060	1.50	<0.005		0.001
	362.00	363.50	566061	1.50	0.006		0.006
	363.50	365.00	566062	1.50	0.057		0.057
	365.00	366.50	566063	1.50	<0.005		0.001
	366.50	368.00	566065	1.50	0.041		0.041
	368.00	369.50	566066	1.50	0.011		0.011
	369.50	370.70	566067	1.20	0.054		0.054
	370.70	371.70	566068	1.00	0.014		0.014
	371.70	373.00	566069	1.30	0.374		0.374
	373.00	374.50	566070	1.50	0.006		0.006
	374.50	376.00	566071	1.50	0.005		0.005
	376.00	377.50	566072	1.50	0.011		0.011
	377.50	379.00	566073	1.50	4.810		4.490
	379.00	380.50	566075	1.50	<0.005		0.001
	380.50	382.00	566076	1.50	<0.005		0.001
	382.00	383.50	566077	1.50	0.007		0.007
	383.50	385.00	566078	1.50	<0.005		0.001
	385.00	386.50	566079	1.50	<0.005		0.001
	386.50	388.00	566080	1.50	0.005		0.005
	388.00	389.50	566081	1.50	0.005		0.005
	389.50	391.00	566082	1.50	<0.005		0.001
	391.00	392.50	566083	1.50	0.006		0.006
392.50	394.00	566085	1.50	0.011	0.011		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			394.00	395.50	566086	1.50	0.018		0.018
			395.50	397.00	566087	1.50	0.014		0.014
			397.00	398.50	566088	1.50	0.005		0.005
			398.50	400.00	566089	1.50	<0.005		0.001
			400.00	401.50	566090	1.50	<0.005		0.001
			401.50	403.00	566091	1.50	<0.005		0.001
			403.00	404.50	566092	1.50	<0.005		0.001
			404.50	406.00	566093	1.50	<0.005		0.001
			406.00	407.50	566095	1.50	<0.005		0.001
			407.50	409.00	566096	1.50	<0.005		0.001
			409.00	410.50	566097	1.50	<0.005		0.001
			410.50	412.00	566098	1.50	<0.005		0.001
			412.00	413.00	566099	1.00	0.005		0.005
			413.00	414.00	566100	1.00	<0.005		0.001
			414.00	415.20	566101	1.20	3.000	2.95	2.950
			415.20	416.30	566102	1.10	0.194		0.194
			416.30	417.50	566103	1.20	0.012		0.012
			417.50	419.00	566104	1.50	<0.005		0.001
			419.00	420.50	566106	1.50	<0.005		0.001
			420.50	422.00	566107	1.50	0.021		0.021
			422.00	423.30	566108	1.30	1.000		1.000
			423.30	424.60	566109	1.30	0.016		0.016
424.60	426.60	SY	424.60	425.60	566110	1.00	2.140		2.140
		<b>Syénite</b>	425.60	426.60	566111	1.00	5.890	5.76	5.760
		Syénite							
426.60	459.20	BA	426.60	428.00	566112	1.40	0.302		0.302
		<b>Basalte</b>	428.00	429.00	566113	1.00	0.006		0.006
		Basalte	429.00	430.50	566115	1.50	0.006		0.006
			430.50	432.00	566116	1.50	0.005		0.005
			432.00	433.50	566117	1.50	0.006		0.006
			433.50	435.00	566118	1.50	0.007		0.007
			435.00	436.20	566119	1.20	<0.005		0.001
			436.20	437.40	566120	1.20	0.028		0.028
			437.40	439.00	566121	1.60	0.094		0.094

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	439.00	440.50	566122	1.50	0.259		0.259
	440.50	442.00	566123	1.50	<0.005		0.001
	442.00	443.50	566125	1.50	0.006		0.006
	443.50	445.00	566126	1.50	<0.005		0.001
	445.00	446.50	566127	1.50	0.013		0.013
	446.50	448.00	566128	1.50	<0.005		0.001
	448.00	449.50	566129	1.50	0.010		0.010
	449.50	450.50	566130	1.00	0.008		0.008
	450.50	452.00	566131	1.50	<0.005		0.001
	452.00	453.50	566132	1.50	<0.005		0.001
	453.50	454.50	566133	1.00	0.145		0.145
	454.50	455.50	566135	1.00	0.007		0.007
	455.50	456.50	566136	1.00	1.275		1.275
	456.50	458.00	566137	1.50	0.008		0.008
	458.00	459.20	566138	1.20	0.043		0.043
459.20	Fin du sondage Nombre d'échantillons : 310 Nombre d'échantillons QAQC : 34 Longueur totale échantillonnée : 456.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
16.00	16.00	565804	565803	0.00	0.325	0.325
29.50	29.50	565814	A3	0.00	0.605	0.605
43.00	43.00	565824	565823	0.00	<0.005	0.001
56.50	56.50	565834	B4	0.00	2.630	2.630
70.00	70.00	565844	565843	0.00	0.015	0.015
83.50	83.50	565854	M1	0.00	<0.005	0.001
97.00	97.00	565864	565863	0.00	0.028	0.028
110.50	110.50	565874	C3	0.00	1.110	1.110
124.00	124.00	565884	565883	0.00	<0.005	0.001
137.50	137.50	565894	D2	0.00	0.882	0.882
151.00	151.00	565904	565903	0.00	0.336	0.336
164.50	164.50	565914	M1	0.00	<0.005	0.001
178.00	178.00	565924	565923	0.00	0.054	0.054
191.50	191.50	565934	G2	0.00	3.990	3.990
205.00	205.00	565944	565943	0.00	0.008	0.008
218.50	218.50	565954	H	0.00	0.933	0.933
232.00	232.00	565964	565963	0.00	0.015	0.015
245.50	245.50	565974	M1	0.00	<0.005	0.001
259.00	259.00	565984	565983	0.00	0.467	0.467
272.50	272.50	565994	A3	0.00	0.624	0.624
286.00	286.00	566004	566003	0.00	0.012	0.012
299.50	299.50	566014	B4	0.00	2.630	2.630
312.50	312.50	566024	566023	0.00	<0.005	0.001
326.00	326.00	566034	M1	0.00	<0.005	0.001
339.50	339.50	566044	566043	0.00	<0.005	0.001
353.00	353.00	566054	F2	0.00	8.420	8.560
366.50	366.50	566064	566063	0.00	<0.005	0.001
379.00	379.00	566074	C3	0.00	1.400	1.400
392.50	392.50	566084	566083	0.00	0.008	0.008
406.00	406.00	566094	M1	0.00	<0.005	0.001
419.00	419.00	566105	566104	0.00	<0.005	0.001
429.00	429.00	566114	D2	0.00	0.916	0.916
442.00	454.50	566134	G2	12.50	4.060	4.030

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
442.00	442.00	566124	566123	0.00	0.007	0.007

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-113**

Titre minier :

Section :                      630900

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              bradley

Lot :

Décrit par :          Gilles.Kamta

Du :                      2010-02-17

Date de description :

Au :                     2010-02-20

Collet

UTM

Azimut :                0.00°

Plongée :              -60.00°

Longueur :            276.90 m

Est                      630 900.0

Nord                    5 374 459.9

Élévation             307.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	8.40°	-60.10°	Oui
Reflex	3.00	358.20°	-60.20°	Oui
Reflex	6.00	358.00°	-60.20°	Oui
Reflex	9.00	24.40°	-60.30°	Oui
Reflex	12.00	350.00°	-60.50°	Oui
Reflex	15.00	165.00°	-60.30°	Oui
Reflex	18.00	359.90°	-60.20°	Non
Reflex	21.00	0.50°	-59.90°	Non
Reflex	24.00	359.30°	-59.50°	Non
Reflex	27.00	358.90°	-59.20°	Non
Reflex	30.00	359.10°	-59.00°	Non
Reflex	33.00	359.10°	-58.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	359.70°	-58.70°	Non
Reflex	39.00	358.30°	-58.50°	Non
Reflex	42.00	358.30°	-58.30°	Non
Reflex	45.00	359.30°	-58.10°	Non
Reflex	48.00	358.50°	-57.60°	Non
Reflex	51.00	359.10°	-57.70°	Non
Reflex	54.00	358.70°	-57.70°	Non
Reflex	57.00	358.10°	-57.70°	Non
Reflex	60.00	358.60°	-57.60°	Non
Reflex	63.00	357.20°	-57.40°	Non
Reflex	66.00	357.10°	-57.30°	Non
Reflex	69.00	357.10°	-57.20°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	72.00	357.80°	-57.30°	Non	Reflex	171.00	359.90°	-56.60°	Non
Reflex	75.00	356.80°	-57.10°	Non	Reflex	174.00	0.00°	-56.70°	Non
Reflex	78.00	357.10°	-57.20°	Non	Reflex	177.00	0.20°	-56.50°	Non
Reflex	81.00	358.20°	-57.00°	Non	Reflex	180.00	0.20°	-56.60°	Non
Reflex	84.00	358.20°	-57.10°	Non	Reflex	183.00	359.80°	-56.60°	Non
Reflex	87.00	356.70°	-57.00°	Non	Reflex	186.00	358.40°	-56.40°	Non
Reflex	90.00	357.50°	-57.10°	Non	Reflex	189.00	358.70°	-56.50°	Non
Reflex	93.00	357.80°	-57.00°	Non	Reflex	192.00	0.50°	-56.50°	Non
Reflex	96.00	357.20°	-57.20°	Non	Reflex	195.00	356.60°	-56.50°	Oui
Reflex	99.00	356.70°	-57.00°	Non	Reflex	198.00	358.60°	-56.50°	Non
Reflex	102.00	358.40°	-56.80°	Oui	Reflex	201.00	359.80°	-56.60°	Non
Reflex	105.00	356.90°	-56.90°	Non	Reflex	204.00	0.10°	-56.40°	Non
Reflex	108.00	356.70°	-56.80°	Non	Reflex	207.00	357.80°	-56.30°	Non
Reflex	111.00	357.60°	-56.80°	Non	Reflex	210.00	3.80°	-56.40°	Oui
Reflex	114.00	357.20°	-56.80°	Non	Reflex	213.00	1.30°	-56.60°	Non
Reflex	117.00	357.90°	-56.80°	Non	Reflex	216.00	0.80°	-56.60°	Non
Reflex	120.00	359.60°	-56.80°	Non	Reflex	219.00	0.30°	-56.60°	Non
Reflex	123.00	0.40°	-56.80°	Non	Reflex	222.00	0.30°	-56.60°	Non
Reflex	126.00	359.70°	-56.90°	Non	Reflex	225.00	0.90°	-56.40°	Non
Reflex	129.00	358.30°	-56.80°	Non	Reflex	228.00	1.50°	-56.50°	Non
Reflex	132.00	358.80°	-56.80°	Non	Reflex	231.00	3.30°	-56.60°	Oui
Reflex	135.00	359.10°	-56.80°	Non	Reflex	234.00	358.70°	-56.30°	Non
Reflex	138.00	358.90°	-56.60°	Non	Reflex	237.00	0.10°	-56.50°	Non
Reflex	141.00	359.40°	-56.50°	Non	Reflex	240.00	359.40°	-56.30°	Non
Reflex	144.00	0.70°	-56.60°	Non	Reflex	243.00	1.30°	-56.50°	Non
Reflex	147.00	358.20°	-56.50°	Non	Reflex	246.00	1.30°	-56.50°	Non
Reflex	150.00	1.90°	-56.70°	Non	Reflex	249.00	359.10°	-56.30°	Non
Reflex	153.00	357.90°	-56.50°	Non	Reflex	252.00	0.20°	-56.30°	Non
Reflex	156.00	359.50°	-56.50°	Non	Reflex	255.00	1.40°	-56.50°	Non
Reflex	159.00	0.00°	-56.50°	Non	Reflex	258.00	355.10°	-56.30°	Oui
Reflex	162.00	0.20°	-56.50°	Non	Reflex	261.00	357.20°	-56.50°	Non
Reflex	165.00	1.50°	-56.70°	Non					
Reflex	168.00	0.60°	-56.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	10.80	MT <b>Mort-terrain</b> MT						
10.80	26.20	SY <b>Syénite</b> Syénite	10.80	12.00	565597	1.20	0.007	0.007
			12.00	13.50	565598	1.50	<0.005	0.001
			13.50	15.00	565599	1.50	<0.005	0.001
			15.00	16.20	565600	1.20	0.005	0.005
			16.20	17.50	565601	1.30	0.009	0.009
			17.50	19.00	565602	1.50	0.067	0.067
			19.00	20.00	565603	1.00	0.010	0.010
			20.00	21.50	565604	1.50	<0.005	0.001
			21.50	23.00	565605	1.50	0.013	0.013
			23.00	24.00	565607	1.00	0.081	0.081
			24.00	25.00	565608	1.00	0.076	0.076
			25.00	26.20	565609	1.20	0.083	0.083
26.20	27.00	NR <b>Carotte perdue</b> LOST						
27.00	268.40	SY <b>Syénite</b> Syénite	27.00	28.50	565610	1.50	<0.005	0.001
			28.50	30.00	565611	1.50	<0.005	0.001
			30.00	31.50	565612	1.50	<0.005	0.001
			31.50	33.00	565613	1.50	0.005	0.005
			33.00	34.50	565614	1.50	<0.005	0.001
			34.50	36.00	565615	1.50	<0.005	0.001
			36.00	37.00	565617	1.00	<0.005	0.001
			37.00	38.50	565618	1.50	<0.005	0.001
			38.50	40.00	565619	1.50	<0.005	0.001
			40.00	41.50	565620	1.50	<0.005	0.001
			41.50	43.00	565621	1.50	<0.005	0.001
			43.00	44.50	565622	1.50	<0.005	0.001
			44.50	46.00	565623	1.50	0.034	0.034
			46.00	47.00	565624	1.00	0.064	0.064
			47.00	48.50	565625	1.50	0.018	0.018
			48.50	50.00	565627	1.50	0.009	0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.50	565628	1.50	0.214		0.214
	51.50	53.00	565629	1.50	0.033		0.033
	53.00	54.50	565630	1.50	0.077		0.077
	54.50	56.00	565631	1.50	0.005		0.005
	56.00	57.50	565632	1.50	0.030		0.030
	57.50	59.00	565633	1.50	0.009		0.009
	59.00	60.50	565634	1.50	0.015		0.015
	60.50	62.00	565635	1.50	1.520		1.520
	62.00	63.50	565637	1.50	0.034		0.034
	63.50	65.00	565638	1.50	0.039		0.039
	65.00	66.50	565639	1.50	<0.005		0.001
	66.50	68.00	565640	1.50	<0.005		0.001
	68.00	69.50	565641	1.50	0.139		0.139
	69.50	71.00	565642	1.50	0.469		0.469
	71.00	72.50	565643	1.50	0.010		0.010
	72.50	74.00	565644	1.50	0.072		0.072
	74.00	75.50	565645	1.50	0.014		0.014
	75.50	77.00	565647	1.50	<0.005		0.001
	77.00	78.50	565648	1.50	<0.005		0.001
	78.50	80.00	565649	1.50	0.039		0.039
	80.00	81.50	565650	1.50	0.133		0.133
	81.50	83.00	565651	1.50	<0.005		0.001
	83.00	84.50	565652	1.50	0.012		0.012
	84.50	86.00	565653	1.50	<0.005		0.001
	86.00	87.50	565654	1.50	<0.005		0.001
	87.50	89.00	565655	1.50	<0.005		0.001
	89.00	90.50	565657	1.50	<0.005		0.001
	90.50	92.00	565658	1.50	<0.005		0.001
	92.00	93.50	565659	1.50	<0.005		0.001
	93.50	95.00	565660	1.50	<0.005		0.001
	95.00	96.50	565661	1.50	<0.005		0.001
	96.50	98.00	565662	1.50	<0.005		0.001
	98.00	99.50	565663	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	99.50	101.00	565664	1.50	0.005		0.005
	101.00	102.50	565665	1.50	<0.005		0.001
	102.50	104.00	565667	1.50	0.006		0.006
	104.00	105.50	565668	1.50	0.139		0.139
	105.50	107.00	565669	1.50	0.012		0.012
	107.00	108.50	565670	1.50	<0.005		0.001
	108.50	110.00	565671	1.50	0.008		0.008
	110.00	111.50	565672	1.50	0.006		0.006
	111.50	113.00	565673	1.50	0.005		0.005
	113.00	114.50	565674	1.50	0.008		0.008
	114.50	116.00	565675	1.50	0.043		0.043
	116.00	117.50	565677	1.50	<0.005		0.001
	117.50	119.00	565678	1.50	0.042		0.042
	119.00	120.50	565679	1.50	0.010		0.010
	120.50	122.00	565680	1.50	0.007		0.007
	122.00	123.50	565681	1.50	0.132		0.132
	123.50	125.00	565682	1.50	0.019		0.019
	125.00	126.40	565683	1.40	0.129		0.129
	126.40	128.00	565684	1.60	0.155		0.155
	128.00	129.20	565685	1.20	0.849		0.849
	129.20	130.20	565687	1.00	0.267		0.267
	130.20	131.50	565688	1.30	0.007		0.007
	131.50	133.00	565689	1.50	<0.005		0.001
	133.00	134.50	565690	1.50	0.170		0.170
	134.50	136.00	565691	1.50	0.787		0.787
	136.00	137.50	565692	1.50	0.161		0.161
	137.50	139.00	565693	1.50	0.008		0.008
	139.00	140.50	565694	1.50	<0.005		0.001
	140.50	142.00	565695	1.50	0.036		0.036
	142.00	143.50	565697	1.50	0.014		0.014
	143.50	145.00	565698	1.50	0.023		0.023
	145.00	146.50	565699	1.50	0.096		0.096
	146.50	148.00	565700	1.50	0.048		0.048

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.00	149.50	565701	1.50	0.082		0.082
	149.50	151.00	565702	1.50	<0.005		0.001
	151.00	152.50	565703	1.50	0.005		0.005
	152.50	154.00	565704	1.50	0.005		0.005
	154.00	155.50	565705	1.50	<0.005		0.001
	155.50	157.00	565707	1.50	<0.005		0.001
	157.00	158.50	565708	1.50	0.014		0.014
	158.50	160.00	565709	1.50	0.006		0.006
	160.00	161.50	565710	1.50	0.021		0.021
	161.50	163.00	565711	1.50	<0.005		0.001
	163.00	164.50	565712	1.50	0.006		0.006
	164.50	166.00	565713	1.50	0.746		0.746
	166.00	167.50	565714	1.50	0.411		0.411
	167.50	169.00	565715	1.50	0.156		0.156
	169.00	170.10	565717	1.10	0.162		0.162
	170.10	171.10	565718	1.00	0.101		0.101
	171.10	172.60	565719	1.50	0.368		0.368
	172.60	174.00	565720	1.40	0.025		0.025
	174.00	175.50	565721	1.50	<0.005		0.001
	175.50	177.00	565722	1.50	1.275		1.275
	177.00	178.50	565723	1.50	0.439		0.439
	178.50	180.00	565724	1.50	0.054		0.054
	180.00	181.30	565725	1.30	0.173		0.173
	181.30	182.40	565727	1.10	0.343		0.343
	182.40	183.80	565728	1.40	0.310		0.310
	183.80	185.00	565729	1.20	0.151		0.151
	185.00	186.50	565730	1.50	0.195		0.195
	186.50	188.00	565731	1.50	0.246		0.246
	188.00	189.50	565732	1.50	1.395		1.395
	189.50	191.00	565733	1.50	0.177		0.177
	191.00	192.50	565734	1.50	<0.005		0.001
	192.50	194.00	565735	1.50	0.024		0.024
	194.00	195.50	565737	1.50	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	195.50	197.00	565738	1.50	<0.005		0.001
	197.00	198.50	565739	1.50	0.008		0.008
	198.50	200.00	565740	1.50	0.099		0.099
	200.00	201.50	565741	1.50	1.770		1.770
	201.50	203.00	565742	1.50	0.418		0.418
	203.00	204.30	565743	1.30	0.314		0.314
	204.30	205.40	565744	1.10	0.008		0.008
	205.40	206.40	565745	1.00	0.644		0.644
	206.40	207.40	565747	1.00	0.993		0.993
	207.40	209.00	565748	1.60	1.105		1.105
	209.00	210.50	565749	1.50	0.916		0.916
	210.50	212.00	565750	1.50	0.020		0.020
	212.00	213.50	565751	1.50	0.191		0.191
	213.50	215.00	565752	1.50	0.206		0.206
	215.00	216.50	565753	1.50	0.524		0.524
	216.50	218.00	565754	1.50	0.528		0.528
	218.00	219.50	565755	1.50	0.195		0.195
	219.50	221.00	565757	1.50	0.106		0.106
	221.00	222.50	565758	1.50	0.041		0.041
	222.50	224.00	565759	1.50	0.073		0.073
	224.00	225.50	565760	1.50	0.611		0.611
	225.50	227.00	565761	1.50	0.012		0.012
	227.00	228.50	565762	1.50	0.152		0.152
	228.50	230.00	565763	1.50	0.120		0.120
	230.00	231.50	565764	1.50	0.378		0.378
	231.50	233.00	565765	1.50	0.131		0.131
	233.00	234.50	565767	1.50	0.106		0.106
	234.50	236.00	565768	1.50	0.189		0.189
	236.00	237.50	565769	1.50	0.096		0.096
	237.50	239.00	565770	1.50	0.027		0.027
	239.00	240.50	565771	1.50	<0.005		0.001
	240.50	242.00	565772	1.50	<0.005		0.001
	242.00	243.50	565773	1.50	0.167		0.167

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			243.50	245.00	565774	1.50	<0.005		0.001
			245.00	246.50	565775	1.50	0.044		0.044
			246.50	248.00	565777	1.50	<0.005		0.001
			248.00	249.50	565778	1.50	<0.005		0.001
			249.50	251.00	565779	1.50	<0.005		0.001
			251.00	252.50	565780	1.50	0.008		0.008
			252.50	253.70	565781	1.20	0.085		0.085
			253.70	254.80	565782	1.10	0.104		0.104
			254.80	256.00	565783	1.20	0.067		0.067
			256.00	257.50	565784	1.50	0.113		0.113
			257.50	259.00	565785	1.50	0.223		0.223
			259.00	260.00	565787	1.00	0.076		0.076
			260.00	261.00	565788	1.00	1.440		1.440
			261.00	262.50	565789	1.50	2.310		2.310
			262.50	264.00	565790	1.50	2.300		2.300
			264.00	265.50	565791	1.50	6.070		6.070
			265.50	267.00	565792	1.50	3.140		3.140
			267.00	268.40	565793	1.40	0.647		0.647
268.40	275.60	OM Ouverture minière OPEN							
275.60	276.90	SY Syénite Syénite	275.60	276.90	565794	1.30	8.500		8.500
276.90	Fin du sondage Nombre d'échantillons : 179 Nombre d'échantillons QAQC : 19 Longueur totale échantillonnée : 258.10								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
23.00	23.00	565606	565605	0.00	<0.005	0.001
36.00	36.00	565616	A3	0.00	0.571	0.571
48.50	48.50	565626	565625	0.00	0.010	0.010
62.00	62.00	565636	B4	0.00	2.660	2.660
75.50	75.50	565646	565645	0.00	0.010	0.010
89.00	89.00	565656	M1	0.00	<0.005	0.001
102.50	102.50	565666	565665	0.00	<0.005	0.001
116.00	116.00	565676	C3	0.00	1.295	1.295
129.20	129.20	565686	565685	0.00	0.928	0.928
142.00	142.00	565696	D2	0.00	0.850	0.850
155.50	155.50	565706	565705	0.00	<0.005	0.001
169.00	169.00	565716	M1	0.00	<0.005	0.001
181.30	181.30	565726	565725	0.00	0.147	0.147
194.00	194.00	565736	G2	0.00	4.090	4.090
206.40	206.40	565746	565745	0.00	0.657	0.657
219.50	219.50	565756	H	0.00	0.967	0.967
233.00	233.00	565766	565765	0.00	0.125	0.125
246.50	259.00	565786	565785	12.50	0.226	0.226
246.50	246.50	565776	M1	0.00	<0.005	0.001





Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	181.30°	-60.40°	Non	Reflex	173.00	182.70°	-60.10°	Non
Reflex	77.00	181.30°	-60.30°	Non	Reflex	176.00	182.40°	-60.10°	Non
Reflex	80.00	180.80°	-60.40°	Non	Reflex	179.00	182.80°	-60.20°	Non
Reflex	83.00	182.00°	-60.50°	Non	Reflex	182.00	183.10°	-60.10°	Non
Reflex	86.00	182.20°	-60.30°	Non	Reflex	185.00	182.90°	-60.20°	Non
Reflex	89.00	181.00°	-60.50°	Non	Reflex	188.00	183.30°	-60.00°	Non
Reflex	92.00	182.10°	-60.40°	Non	Reflex	191.00	183.40°	-60.10°	Non
Reflex	95.00	181.60°	-60.40°	Non	Reflex	194.00	183.60°	-60.00°	Non
Reflex	98.00	182.80°	-60.30°	Non	Reflex	197.00	183.50°	-60.00°	Non
Reflex	101.00	184.10°	-60.40°	Oui	Reflex	200.00	184.00°	-60.00°	Non
Reflex	104.00	183.60°	-60.30°	Non	Reflex	203.00	183.00°	-60.10°	Non
Reflex	107.00	183.00°	-60.40°	Non	Reflex	206.00	183.60°	-60.00°	Non
Reflex	110.00	183.20°	-60.30°	Non	Reflex	209.00	183.50°	-59.90°	Non
Reflex	113.00	183.50°	-60.40°	Non	Reflex	212.00	183.60°	-60.00°	Non
Reflex	116.00	183.70°	-60.20°	Non	Reflex	215.00	183.40°	-60.00°	Non
Reflex	119.00	182.00°	-60.50°	Non	Reflex	218.00	182.90°	-60.10°	Non
Reflex	122.00	182.30°	-60.30°	Non	Reflex	221.00	182.80°	-60.00°	Non
Reflex	125.00	182.60°	-60.30°	Non	Reflex	224.00	183.10°	-59.90°	Non
Reflex	128.00	182.00°	-60.30°	Non	Reflex	227.00	183.00°	-60.00°	Non
Reflex	131.00	182.10°	-60.40°	Non	Reflex	230.00	183.50°	-59.90°	Non
Reflex	134.00	183.20°	-60.30°	Non	Reflex	233.00	183.20°	-59.90°	Non
Reflex	137.00	183.00°	-60.10°	Non	Reflex	236.00	183.40°	-60.00°	Non
Reflex	140.00	182.10°	-60.20°	Non	Reflex	239.00	183.50°	-59.80°	Non
Reflex	143.00	183.30°	-60.20°	Non	Reflex	242.00	183.60°	-59.90°	Non
Reflex	146.00	183.00°	-60.10°	Non	Reflex	245.00	183.50°	-59.80°	Non
Reflex	149.00	183.30°	-60.20°	Non	Reflex	248.00	183.20°	-60.00°	Non
Reflex	152.00	183.30°	-60.20°	Non	Reflex	251.00	183.80°	-59.70°	Non
Reflex	155.00	183.20°	-60.20°	Non	Reflex	254.00	184.20°	-59.80°	Non
Reflex	158.00	182.80°	-60.30°	Non	Reflex	257.00	183.80°	-59.80°	Non
Reflex	161.00	182.60°	-60.30°	Non	Reflex	260.00	183.60°	-59.80°	Non
Reflex	164.00	182.30°	-60.10°	Non	Reflex	263.00	183.90°	-59.90°	Non
Reflex	167.00	182.60°	-60.30°	Non	Reflex	266.00	183.30°	-59.70°	Non
Reflex	170.00	182.10°	-60.10°	Non	Reflex	269.00	183.70°	-59.80°	Non

Corporation Minière Osisko Div. Exploration

Déviaton

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	184.10°	-59.80°	Non					
Reflex	275.00	184.20°	-59.60°	Non					
Reflex	278.00	183.40°	-59.60°	Non					
Reflex	281.00	184.40°	-59.70°	Non					
Reflex	284.00	183.10°	-59.70°	Non					
Reflex	287.00	183.80°	-59.50°	Non					
Reflex	290.00	183.70°	-59.60°	Non					
Reflex	293.00	182.60°	-59.60°	Non					
Reflex	296.00	185.40°	-59.40°	Non					
Reflex	299.00	184.70°	-59.40°	Non					
Reflex	302.00	183.50°	-59.40°	Non					
Reflex	305.00	183.60°	-59.40°	Non					
Reflex	308.00	185.00°	-59.40°	Oui					
Reflex	311.00	183.40°	-59.20°	Non					
Reflex	314.00	184.80°	-59.30°	Non					
Reflex	317.00	184.60°	-59.20°	Non					
Reflex	320.00	184.00°	-59.30°	Non					
Reflex	323.00	184.70°	-59.40°	Non					
Reflex	326.00	184.10°	-59.30°	Non					
Reflex	329.00	181.60°	-59.20°	Oui					
Reflex	332.00	185.60°	-59.10°	Non					
Reflex	335.00	179.30°	-59.10°	Non					
Reflex	338.00	179.80°	-59.10°	Non					
Reflex	341.00	182.90°	-59.30°	Non					
Reflex	344.00	183.10°	-59.10°	Non					
Reflex	347.00	182.40°	-59.10°	Non					
Reflex	350.00	186.00°	-59.00°	Oui					
Reflex	353.00	184.30°	-58.90°	Non					
Reflex	356.00	184.30°	-59.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	11.50	MT Mort-terrain MT						
11.50	252.10	SY Syénite Syénite	11.50	13.00	149926	1.50	<0.005	0.001
			13.00	14.50	149927	1.50	0.016	0.016
			14.50	16.00	149928	1.50	0.071	0.071
			16.00	17.50	149929	1.50	0.010	0.010
			17.50	19.00	149930	1.50	0.005	0.005
			19.00	20.50	149931	1.50	<0.005	0.001
			20.50	22.00	149932	1.50	0.018	0.018
			22.00	23.50	149933	1.50	0.009	0.009
			23.50	25.00	149934	1.50	<0.005	0.001
			25.00	26.50	149935	1.50	<0.005	0.001
			26.50	28.00	149936	1.50	<0.005	0.001
			28.00	29.50	149938	1.50	<0.005	0.001
			29.50	31.00	149939	1.50	0.006	0.006
			31.00	32.50	149940	1.50	0.015	0.015
			32.50	34.00	149941	1.50	<0.005	0.001
			34.00	35.50	149942	1.50	0.009	0.009
			35.50	37.00	149943	1.50	<0.005	0.001
			37.00	38.50	149944	1.50	<0.005	0.001
			38.50	40.00	149945	1.50	<0.005	0.001
			40.00	41.50	149947	1.50	0.006	0.006
			41.50	43.00	149948	1.50	0.007	0.007
			43.00	44.50	149949	1.50	<0.005	0.001
			44.50	46.00	149950	1.50	<0.005	0.001
			46.00	46.80	149951	0.80	<0.005	0.001
			46.80	48.50	149952	1.70	<0.005	0.001
			48.50	50.00	149953	1.50	<0.005	0.001
			50.00	51.50	149954	1.50	0.020	0.020
			51.50	53.00	149955	1.50	<0.005	0.001
			53.00	54.50	149956	1.50	<0.005	0.001
			54.50	56.00	149957	1.50	<0.005	0.001
			56.00	57.50	149959	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	57.50	59.00	149960	1.50	0.031		0.031
	59.00	60.50	149961	1.50	0.009		0.009
	60.50	62.00	149962	1.50	<0.005		0.001
	62.00	63.50	149963	1.50	<0.005		0.001
	63.50	65.00	149964	1.50	<0.005		0.001
	65.00	66.50	149965	1.50	<0.005		0.001
	66.50	68.00	149967	1.50	<0.005		0.001
	68.00	69.50	149968	1.50	<0.005		0.001
	69.50	71.00	149969	1.50	<0.005		0.001
	71.00	72.50	149970	1.50	<0.005		0.001
	72.50	74.00	149971	1.50	<0.005		0.001
	74.00	75.50	149972	1.50	0.039		0.039
	75.50	77.00	149973	1.50	0.035		0.035
	77.00	78.50	149974	1.50	<0.005		0.001
	78.50	80.00	149975	1.50	0.006		0.006
	80.00	81.50	149976	1.50	0.005		0.005
	81.50	83.00	149977	1.50	0.036		0.036
	83.00	84.50	149979	1.50	0.010		0.010
	84.50	86.00	149980	1.50	<0.005		0.001
	86.00	87.50	149981	1.50	0.005		0.005
	87.50	89.00	149982	1.50	0.020		0.020
	89.00	90.50	149983	1.50	0.021		0.021
	90.50	92.00	149984	1.50	0.049		0.049
	92.00	93.50	149985	1.50	0.021		0.021
	93.50	95.00	149987	1.50	<0.005		0.001
	95.00	96.50	149988	1.50	0.012		0.012
	96.50	98.00	149989	1.50	0.018		0.018
	98.00	99.50	149990	1.50	<0.005		0.001
	99.50	101.00	149991	1.50	0.007		0.007
	101.00	102.50	149992	1.50	<0.005		0.001
	102.50	104.00	149993	1.50	<0.005		0.001
	104.00	105.50	149994	1.50	0.006		0.006
	105.50	107.00	149995	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	107.00	108.50	149996	1.50	<0.005		0.001
	108.50	110.00	149997	1.50	0.005		0.005
	110.00	111.50	149999	1.50	0.007		0.007
	111.50	113.00	150000	1.50	0.186		0.186
	113.00	114.50	150001	1.50	0.011		0.011
	114.50	115.50	150002	1.00	0.893		0.893
	115.50	117.00	150003	1.50	1.475		1.475
	117.00	118.50	150004	1.50	0.505		0.505
	118.50	120.00	150005	1.50	0.041		0.041
	120.00	121.50	150007	1.50	1.055		1.055
	121.50	123.00	150008	1.50	0.949		0.949
	123.00	124.50	150009	1.50	3.480	3.54	3.540
	124.50	126.00	150010	1.50	1.865		1.865
	126.00	127.00	150011	1.00	2.650		2.650
	127.00	128.00	150012	1.00	1.635		1.635
	128.00	129.50	150013	1.50	1.320		1.320
	129.50	130.50	150014	1.00	0.258		0.258
	130.50	131.50	150015	1.00	0.076		0.076
	131.50	133.00	150016	1.50	0.112		0.112
	133.00	134.50	150017	1.50	0.097		0.097
	134.50	136.00	150019	1.50	0.140		0.140
	136.00	137.50	150020	1.50	0.048		0.048
	137.50	139.00	150021	1.50	0.096		0.096
	139.00	140.50	150022	1.50	0.303		0.303
	140.50	142.00	150023	1.50	0.147		0.147
	142.00	143.50	150024	1.50	0.095		0.095
	143.50	145.00	150025	1.50	0.237		0.237
	145.00	146.50	150027	1.50	0.052		0.052
	146.50	148.00	150028	1.50	0.419		0.419
	148.00	149.50	150029	1.50	0.129		0.129
	149.50	151.00	150030	1.50	0.135		0.135
	151.00	152.50	150031	1.50	0.074		0.074
	152.50	154.00	150032	1.50	0.039		0.039

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	154.00	155.50	150033	1.50	0.082		0.082
	155.50	157.00	150034	1.50	0.243		0.243
	157.00	158.00	150035	1.00	0.513		0.513
	158.00	159.50	150036	1.50	0.037		0.037
	159.50	161.00	150037	1.50	0.044		0.044
	161.00	162.50	150039	1.50	0.102		0.102
	162.50	164.00	150040	1.50	0.067		0.067
	164.00	165.50	150041	1.50	0.629		0.629
	165.50	167.00	150042	1.50	0.609		0.609
	167.00	168.50	150043	1.50	0.113		0.113
	168.50	170.00	150044	1.50	0.066		0.066
	170.00	171.50	150045	1.50	0.172		0.172
	171.50	173.00	150047	1.50	0.173		0.173
	173.00	174.50	150048	1.50	0.156		0.156
	174.50	176.00	150049	1.50	0.627		0.627
	176.00	177.50	150050	1.50	0.592		0.592
	177.50	179.00	150051	1.50	0.122		0.122
	179.00	180.50	150052	1.50	0.009		0.009
	180.50	182.00	150053	1.50	0.145		0.145
	182.00	183.50	150054	1.50	0.152		0.152
	183.50	185.00	150055	1.50	0.039		0.039
	185.00	186.50	150056	1.50	0.447		0.447
	186.50	188.00	150057	1.50	0.048		0.048
	188.00	189.50	150059	1.50	0.196		0.196
	189.50	191.00	150060	1.50	0.042		0.042
	191.00	192.50	150061	1.50	0.571		0.571
	192.50	194.00	150062	1.50	0.404		0.404
	194.00	195.50	150063	1.50	0.126		0.126
	195.50	197.00	150064	1.50	0.179		0.179
	197.00	198.50	150065	1.50	0.045		0.045
	198.50	200.00	150067	1.50	0.334		0.334
	200.00	201.50	150068	1.50	0.751		0.751
	201.50	203.00	150069	1.50	0.140		0.140

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	203.00	204.50	150070	1.50	0.314		0.314
	204.50	205.50	150071	1.00	0.176		0.176
	205.50	206.50	150072	1.00	0.572		0.572
	206.50	207.50	150073	1.00	0.366		0.366
	207.50	209.00	150074	1.50	0.125		0.125
	209.00	210.50	150075	1.50	0.387		0.387
	210.50	212.00	150076	1.50	0.176		0.176
	212.00	213.50	150077	1.50	1.335		1.335
	213.50	215.00	150079	1.50	0.281		0.281
	215.00	216.50	150080	1.50	0.433		0.433
	216.50	218.00	150081	1.50	0.159		0.159
	218.00	219.50	150082	1.50	0.153		0.153
	219.50	221.00	150083	1.50	0.315		0.315
	221.00	222.50	150084	1.50	0.110		0.110
	222.50	224.00	150085	1.50	0.138		0.138
	224.00	225.00	150087	1.00	0.167		0.167
	225.00	226.50	150088	1.50	0.334		0.334
	226.50	228.00	150089	1.50	1.110		1.110
	228.00	229.50	150090	1.50	0.441		0.441
	229.50	231.00	150091	1.50	0.305		0.305
	231.00	232.50	150092	1.50	0.021		0.021
	232.50	234.00	150093	1.50	0.019		0.019
	234.00	235.50	150094	1.50	0.057		0.057
	235.50	237.00	150095	1.50	0.089		0.089
	237.00	238.50	150096	1.50	0.010		0.010
	238.50	240.00	150097	1.50	0.071		0.071
	240.00	241.50	150099	1.50	0.076		0.076
	241.50	243.00	150100	1.50	0.058		0.058
	243.00	244.50	150101	1.50	0.012		0.012
	244.50	246.00	150102	1.50	0.092		0.092
	246.00	247.50	150103	1.50	0.007		0.007
	247.50	249.00	150104	1.50	0.006		0.006
	249.00	250.50	150105	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
252.10	339.00	BA Basalte Basalte	250.50	252.10	150107	1.60	<0.005		0.001
			252.10	253.50	150108	1.40	0.228		0.228
			253.50	255.00	150109	1.50	<0.005		0.001
			255.00	256.50	150110	1.50	<0.005		0.001
			256.50	258.00	150111	1.50	<0.005		0.001
			258.00	259.50	150112	1.50	<0.005		0.001
			259.50	261.00	150113	1.50	0.005		0.005
			261.00	262.50	150114	1.50	0.024		0.024
			262.50	264.00	150115	1.50	0.093		0.093
			264.00	265.50	150116	1.50	0.005		0.005
			265.50	267.00	150117	1.50	<0.005		0.001
			267.00	268.50	150119	1.50	<0.005		0.001
			268.50	270.00	150120	1.50	<0.005		0.001
			270.00	271.50	150121	1.50	0.005		0.005
			271.50	273.00	150122	1.50	<0.005		0.001
			273.00	274.50	150123	1.50	<0.005		0.001
			274.50	276.00	150124	1.50	<0.005		0.001
			276.00	277.50	150125	1.50	<0.005		0.001
			277.50	279.00	150127	1.50	<0.005		0.001
			279.00	280.50	150128	1.50	<0.005		0.001
			280.50	282.00	150129	1.50	<0.005		0.001
			282.00	283.50	150130	1.50	<0.005		0.001
			283.50	285.00	150131	1.50	<0.005		0.001
			285.00	286.50	150132	1.50	0.028		0.028
			286.50	288.00	150133	1.50	<0.005		0.001
			288.00	289.50	150134	1.50	<0.005		0.001
			289.50	291.00	150135	1.50	<0.005		0.001
			291.00	292.50	150136	1.50	0.022		0.022
292.50	294.00	150137	1.50	<0.005		0.001			
294.00	295.50	150139	1.50	<0.005		0.001			
295.50	297.00	150140	1.50	0.005		0.005			
297.00	298.50	150141	1.50	<0.005		0.001			
298.50	300.00	150142	1.50	0.064		0.064			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			300.00	301.50	150143	1.50	<0.005		0.001
			301.50	303.00	150144	1.50	<0.005		0.001
			303.00	304.50	150145	1.50	0.009		0.009
			304.50	306.00	150147	1.50	0.086		0.086
			306.00	307.50	150148	1.50	<0.005		0.001
			307.50	309.00	150149	1.50	<0.005		0.001
			309.00	310.50	150150	1.50	0.119		0.119
			310.50	312.00	150151	1.50	0.253		0.253
			312.00	313.50	150152	1.50	<0.005		0.001
			313.50	315.00	150153	1.50	<0.005		0.001
			315.00	316.50	150154	1.50	<0.005		0.001
			316.50	318.00	150155	1.50	<0.005		0.001
			318.00	319.50	150156	1.50	<0.005		0.001
			319.50	321.00	150157	1.50	<0.005		0.001
			321.00	322.50	150159	1.50	<0.005		0.001
			322.50	324.00	150160	1.50	<0.005		0.001
			324.00	325.50	150161	1.50	<0.005		0.001
			325.50	327.00	150162	1.50	0.007		0.007
			327.00	328.50	150163	1.50	<0.005		0.001
			328.50	330.00	150164	1.50	<0.005		0.001
			330.00	331.50	150165	1.50	<0.005		0.001
			331.50	333.00	150167	1.50	0.005		0.005
			333.00	334.50	150168	1.50	<0.005		0.001
			334.50	336.00	150169	1.50	<0.005		0.001
			336.00	337.50	150170	1.50	<0.005		0.001
			337.50	339.00	150171	1.50	<0.005		0.001
339.00	356.80	SY	339.00	340.50	150172	1.50	<0.005		0.001
		<b>Syénite</b>	340.50	342.00	150173	1.50	0.199		0.199
		Syénite	342.00	343.50	150174	1.50	<0.005		0.001
			343.50	345.00	150175	1.50	<0.005		0.001
			345.00	346.50	150176	1.50	<0.005		0.001
			346.50	348.00	150177	1.50	0.040		0.040
			348.00	349.50	150179	1.50	0.141		0.141

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	349.50	351.00	150180	1.50	<0.005		0.001
	351.00	352.50	150181	1.50	0.077		0.077
	352.50	354.00	150182	1.50	0.005		0.005
	354.00	355.50	150183	1.50	0.008		0.008
	355.50	356.80	150184	1.30	0.199		0.199
<p>356.80      Fin du sondage                      Nombre d'échantillons : 234                      Nombre d'échantillons QAQC : 25                      Longueur totale échantillonnée : 345.30</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
26.50	28.00	149937	A3	1.50	0.600	0.600
38.50	40.00	149946	149945	1.50	0.007	0.007
54.50	56.00	149958	H	1.50	0.986	0.986
65.00	66.50	149966	149965	1.50	<0.005	0.001
81.50	83.00	149978	M1	1.50	<0.005	0.001
92.00	93.50	149986	149985	1.50	0.021	0.021
108.50	110.00	149998	D2	1.50	0.870	0.870
118.50	120.00	150006	150005	1.50	0.032	0.032
133.00	134.50	150018	B4	1.50	2.570	2.570
143.50	145.00	150026	150025	1.50	0.048	0.048
159.50	161.00	150038	M1	1.50	<0.005	0.001
170.00	171.50	150046	150045	1.50	0.182	0.182
186.50	188.00	150058	F2	1.50	8.630	8.480
197.00	198.50	150066	150065	1.50	0.074	0.074
212.00	213.50	150078	C3	1.50	1.385	1.385
222.50	224.00	150086	150085	1.50	0.131	0.131
238.50	240.00	150098	M1	1.50	<0.005	0.001
249.00	250.50	150106	150105	1.50	<0.005	0.001
265.50	267.00	150118	G2	1.50	4.210	4.000
276.00	277.50	150126	150125	1.50	<0.005	0.001
292.50	294.00	150138	A3	1.50	0.620	0.620
303.00	304.50	150146	150145	1.50	0.008	0.008
319.50	321.00	150158	M1	1.50	<0.005	0.001
330.00	331.50	150166	150165	1.50	<0.005	0.001
346.50	348.00	150178	H	1.50	0.989	0.989



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.60°	-59.50°	Non	Reflex	173.00	0.20°	-59.60°	Non
Reflex	77.00	0.90°	-59.70°	Non	Reflex	176.00	358.40°	-59.60°	Oui
Reflex	80.00	1.70°	-59.60°	Non	Reflex	179.00	1.40°	-59.50°	Non
Reflex	83.00	1.50°	-59.60°	Non	Reflex	182.00	2.80°	-59.70°	Non
Reflex	86.00	2.60°	-59.60°	Oui	Reflex	185.00	2.00°	-59.50°	Non
Reflex	89.00	1.30°	-59.60°	Non	Reflex	188.00	1.80°	-59.70°	Non
Reflex	92.00	0.90°	-59.70°	Non	Reflex	191.00	3.90°	-59.50°	Non
Reflex	95.00	1.30°	-59.60°	Non	Reflex	194.00	3.20°	-59.50°	Non
Reflex	98.00	2.00°	-59.70°	Non	Reflex	197.00	2.50°	-59.50°	Non
Reflex	101.00	2.30°	-59.60°	Non	Reflex	200.00	3.70°	-59.60°	Non
Reflex	104.00	1.60°	-59.70°	Non	Reflex	203.00	0.10°	-59.70°	Oui
Reflex	107.00	1.80°	-59.50°	Non	Reflex	206.00	1.90°	-59.50°	Non
Reflex	110.00	1.70°	-59.60°	Non	Reflex	209.00	1.10°	-59.70°	Non
Reflex	113.00	2.10°	-59.50°	Non	Reflex	212.00	1.00°	-59.50°	Non
Reflex	116.00	1.50°	-59.60°	Non	Reflex	215.00	3.10°	-59.70°	Non
Reflex	119.00	0.20°	-59.70°	Non	Reflex	218.00	2.90°	-59.50°	Non
Reflex	122.00	0.20°	-59.50°	Non	Reflex	221.00	2.90°	-59.60°	Non
Reflex	125.00	358.90°	-59.70°	Non	Reflex	224.00	2.20°	-59.60°	Non
Reflex	128.00	0.60°	-59.50°	Non	Reflex	227.00	3.00°	-60.00°	Non
Reflex	131.00	1.60°	-59.40°	Non	Reflex	230.00	1.40°	-59.70°	Non
Reflex	134.00	1.50°	-59.50°	Non	Reflex	233.00	1.30°	-59.70°	Non
Reflex	137.00	1.10°	-59.40°	Non	Reflex	236.00	1.70°	-59.60°	Non
Reflex	140.00	359.80°	-59.50°	Non	Reflex	239.00	1.40°	-59.60°	Non
Reflex	143.00	358.50°	-59.50°	Non	Reflex	242.00	2.00°	-59.50°	Non
Reflex	146.00	0.50°	-59.60°	Non	Reflex	245.00	2.00°	-59.60°	Non
Reflex	149.00	0.90°	-59.50°	Non	Reflex	248.00	1.30°	-58.90°	Oui
Reflex	152.00	0.70°	-59.60°	Non	Reflex	251.00	2.00°	-59.40°	Non
Reflex	155.00	2.20°	-59.50°	Non	Reflex	254.00	1.80°	-59.60°	Non
Reflex	158.00	2.80°	-59.40°	Non	Reflex	257.00	2.10°	-59.40°	Non
Reflex	161.00	359.20°	-59.70°	Non	Reflex	260.00	1.90°	-59.40°	Non
Reflex	164.00	0.30°	-59.50°	Non	Reflex	263.00	1.80°	-59.60°	Non
Reflex	167.00	359.90°	-59.60°	Non	Reflex	266.00	1.90°	-59.30°	Non
Reflex	170.00	0.20°	-59.50°	Non	Reflex	269.00	2.30°	-59.30°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	2.10°	-59.20°	Non	Reflex	371.00	2.00°	-58.00°	Non
Reflex	275.00	1.80°	-59.30°	Non	Reflex	374.00	2.20°	-57.90°	Non
Reflex	278.00	2.20°	-59.10°	Non	Reflex	377.00	2.00°	-57.90°	Non
Reflex	281.00	1.70°	-59.20°	Oui	Reflex	380.00	2.10°	-58.00°	Non
Reflex	284.00	2.20°	-59.10°	Non	Reflex	383.00	2.40°	-57.90°	Non
Reflex	287.00	2.20°	-59.30°	Non	Reflex	386.00	2.00°	-57.90°	Non
Reflex	290.00	2.90°	-59.10°	Non	Reflex	389.00	2.20°	-57.90°	Non
Reflex	293.00	2.60°	-59.20°	Non	Reflex	392.00	1.90°	-57.90°	Non
Reflex	296.00	2.40°	-59.10°	Non	Reflex	395.00	2.30°	-57.80°	Non
Reflex	299.00	2.30°	-59.00°	Non	Reflex	398.00	2.30°	-57.80°	Non
Reflex	302.00	2.30°	-59.10°	Non	Reflex	401.00	2.60°	-57.70°	Non
Reflex	305.00	2.10°	-58.70°	Non	Reflex	404.00	2.40°	-57.70°	Non
Reflex	308.00	1.80°	-58.70°	Non					
Reflex	311.00	1.70°	-58.70°	Non					
Reflex	314.00	1.90°	-58.60°	Non					
Reflex	317.00	1.70°	-58.60°	Non					
Reflex	320.00	1.80°	-58.70°	Non					
Reflex	323.00	2.10°	-58.40°	Oui					
Reflex	326.00	1.80°	-58.50°	Non					
Reflex	329.00	2.00°	-58.30°	Non					
Reflex	332.00	1.90°	-58.40°	Non					
Reflex	335.00	2.30°	-58.30°	Non					
Reflex	338.00	1.70°	-58.40°	Non					
Reflex	341.00	2.10°	-58.20°	Non					
Reflex	344.00	1.70°	-58.40°	Non					
Reflex	347.00	1.70°	-58.30°	Non					
Reflex	350.00	1.80°	-58.10°	Non					
Reflex	353.00	1.60°	-58.30°	Non					
Reflex	356.00	1.80°	-58.30°	Non					
Reflex	359.00	2.10°	-58.10°	Non					
Reflex	362.00	2.00°	-58.10°	Non					
Reflex	365.00	1.80°	-58.20°	Non					
Reflex	368.00	2.10°	-58.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.80	MT <b>Mort-terrain</b> MT						
1.80	265.00	SY <b>Syénite</b> Syénite	1.80	3.50	144272	1.70	<0.005	0.001
			3.50	5.00	144273	1.50	<0.005	0.001
			5.00	6.50	144274	1.50	<0.005	0.001
			6.50	8.00	144275	1.50	<0.005	0.001
			8.00	9.50	144276	1.50	<0.005	0.001
			9.50	11.00	144277	1.50	<0.005	0.001
			11.00	12.50	144278	1.50	<0.005	0.001
			12.50	14.00	144279	1.50	0.033	0.033
			14.00	15.40	144280	1.40	<0.005	0.001
			15.40	17.00	144281	1.60	0.039	0.039
			17.00	18.50	144283	1.50	<0.005	0.001
			18.50	20.10	144284	1.60	<0.005	0.001
			20.10	21.80	144285	1.70	<0.005	0.001
			21.80	23.50	144286	1.70	<0.005	0.001
			23.50	25.00	144287	1.50	<0.005	0.001
			25.00	26.50	144288	1.50	<0.005	0.001
			26.50	28.00	144289	1.50	<0.005	0.001
			28.00	29.50	144290	1.50	0.007	0.007
			29.50	31.00	144291	1.50	<0.005	0.001
			31.00	32.50	144293	1.50	<0.005	0.001
			32.50	34.00	144294	1.50	<0.005	0.001
			34.00	35.50	144295	1.50	<0.005	0.001
			35.50	37.00	144296	1.50	0.005	0.005
			37.00	38.50	144297	1.50	0.134	0.134
			38.50	40.00	144298	1.50	0.089	0.089
			40.00	41.50	144299	1.50	0.196	0.196
			41.50	43.00	144300	1.50	0.008	0.008
			43.00	44.50	144301	1.50	<0.005	0.001
			44.50	46.00	144303	1.50	<0.005	0.001
			46.00	47.50	144304	1.50	0.005	0.005
			47.50	49.20	144305	1.70	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.20	50.50	144306	1.30	<0.005		0.001
	50.50	52.00	144307	1.50	0.009		0.009
	52.00	53.50	144308	1.50	<0.005		0.001
	53.50	55.00	144309	1.50	<0.005		0.001
	55.00	56.50	144310	1.50	<0.005		0.001
	56.50	58.00	144311	1.50	<0.005		0.001
	58.00	59.50	144313	1.50	<0.005		0.001
	59.50	61.00	144314	1.50	<0.005		0.001
	61.00	62.50	144315	1.50	<0.005		0.001
	62.50	64.00	144316	1.50	<0.005		0.001
	64.00	65.50	144317	1.50	<0.005		0.001
	65.50	67.00	144318	1.50	<0.005		0.001
	67.00	68.50	144319	1.50	<0.005		0.001
	68.50	70.00	144320	1.50	<0.005		0.001
	70.00	71.50	144321	1.50	0.012		0.012
	71.50	73.20	144323	1.70	0.060		0.060
	73.20	74.90	144324	1.70	<0.005		0.001
	74.90	76.00	144325	1.10	<0.005		0.001
	76.00	77.00	144326	1.00	<0.005		0.001
	77.00	78.50	144327	1.50	0.204		0.204
	78.50	80.00	144328	1.50	0.376		0.376
	80.00	81.00	144329	1.00	0.127		0.127
	81.00	82.50	144330	1.50	<0.005		0.001
	82.50	84.00	144331	1.50	<0.005		0.001
	84.00	85.50	144333	1.50	<0.005		0.001
	85.50	87.00	144334	1.50	0.031		0.031
	87.00	88.50	144335	1.50	0.020		0.020
	88.50	90.00	144336	1.50	0.006		0.006
	90.00	91.00	144337	1.00	0.143		0.143
	91.00	92.00	144338	1.00	0.006		0.006
	92.00	93.00	144339	1.00	0.005		0.005
	93.00	94.50	144340	1.50	0.237		0.237
	94.50	96.00	144341	1.50	0.043		0.043

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	96.00	97.50	144343	1.50	0.026		0.026
	97.50	99.00	144344	1.50	<0.005		0.001
	99.00	100.50	144345	1.50	<0.005		0.001
	100.50	102.00	144346	1.50	0.009		0.009
	102.00	103.50	144347	1.50	<0.005		0.001
	103.50	105.00	144348	1.50	<0.005		0.001
	105.00	106.50	144349	1.50	<0.005		0.001
	106.50	108.00	144350	1.50	<0.005		0.001
	108.00	109.50	144351	1.50	0.008		0.008
	109.50	111.00	144353	1.50	<0.005		0.001
	111.00	112.50	144354	1.50	<0.005		0.001
	112.50	114.00	144355	1.50	<0.005		0.001
	114.00	115.50	144356	1.50	0.005		0.005
	115.50	117.00	144357	1.50	0.334		0.334
	117.00	118.60	144358	1.60	0.365		0.365
	118.60	120.00	144359	1.40	0.180		0.180
	120.00	121.50	144360	1.50	0.262		0.262
	121.50	123.00	144361	1.50	0.010		0.010
	123.00	124.50	144363	1.50	<0.005		0.001
	124.50	126.00	144364	1.50	0.008		0.008
	126.00	127.50	144365	1.50	0.010		0.010
	127.50	129.00	144366	1.50	<0.005		0.001
	129.00	130.50	144367	1.50	0.005		0.005
	130.50	132.00	144368	1.50	<0.005		0.001
	132.00	133.50	144369	1.50	0.009		0.009
	133.50	135.00	144370	1.50	<0.005		0.001
	135.00	136.50	144371	1.50	0.016		0.016
	136.50	138.00	144373	1.50	0.007		0.007
	138.00	139.50	144374	1.50	<0.005		0.001
	139.50	141.00	144375	1.50	<0.005		0.001
	141.00	142.50	144376	1.50	0.050		0.050
	142.50	144.00	144377	1.50	0.010		0.010
	144.00	145.50	144378	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	145.50	147.00	144379	1.50	<0.005		0.001
	147.00	148.50	144380	1.50	<0.005		0.001
	148.50	150.00	144381	1.50	0.005		0.005
	150.00	151.50	144383	1.50	0.018		0.018
	151.50	153.00	144384	1.50	0.061		0.061
	153.00	154.50	144385	1.50	<0.005		0.001
	154.50	156.00	144386	1.50	<0.005		0.001
	156.00	157.50	144387	1.50	<0.005		0.001
	157.50	158.80	144388	1.30	<0.005		0.001
	158.80	160.00	144389	1.20	0.117		0.117
	160.00	161.50	144390	1.50	<0.005		0.001
	161.50	163.00	144391	1.50	<0.005		0.001
	163.00	164.50	144393	1.50	0.064		0.064
	164.50	166.00	144394	1.50	0.950		0.950
	166.00	167.50	144395	1.50	0.727		0.727
	167.50	169.00	144396	1.50	0.087		0.087
	169.00	170.00	144397	1.00	0.073		0.073
	170.00	171.00	144398	1.00	0.010		0.010
	171.00	172.50	144399	1.50	<0.005		0.001
	172.50	174.00	144400	1.50	0.032		0.032
	174.00	175.50	144401	1.50	0.014		0.014
	175.50	177.00	144403	1.50	<0.005		0.001
	177.00	178.50	144404	1.50	<0.005		0.001
	178.50	180.00	144405	1.50	0.007		0.007
	180.00	181.50	144406	1.50	0.013		0.013
	181.50	183.00	144407	1.50	<0.005		0.001
	183.00	184.50	144408	1.50	0.005		0.005
	184.50	186.00	144409	1.50	0.026		0.026
	186.00	187.50	144410	1.50	0.033		0.033
	187.50	189.00	144411	1.50	0.134		0.134
	189.00	190.50	144413	1.50	0.009		0.009
	190.50	192.00	144414	1.50	0.013		0.013
	192.00	193.50	144415	1.50	0.026		0.026

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	193.50	195.00	144416	1.50	0.006		0.006
	195.00	196.50	144417	1.50	<0.005		0.001
	196.50	198.00	144418	1.50	<0.005		0.001
	198.00	199.50	144419	1.50	0.005		0.005
	199.50	201.00	144420	1.50	<0.005		0.001
	201.00	202.50	144421	1.50	<0.005		0.001
	202.50	204.00	144423	1.50	<0.005		0.001
	204.00	205.50	144424	1.50	<0.005		0.001
	205.50	206.60	144425	1.10	<0.005		0.001
	206.60	208.00	144426	1.40	<0.005		0.001
	208.00	209.50	144427	1.50	<0.005		0.001
	209.50	211.00	144428	1.50	0.011		0.011
	211.00	212.50	144429	1.50	0.050		0.050
	212.50	214.00	144430	1.50	0.006		0.006
	214.00	215.50	144431	1.50	0.006		0.006
	215.50	217.00	144433	1.50	<0.005		0.001
	217.00	218.50	144434	1.50	<0.005		0.001
	218.50	220.00	144435	1.50	0.005		0.005
	220.00	221.50	144436	1.50	<0.005		0.001
	221.50	223.00	144437	1.50	<0.005		0.001
	223.00	224.50	144438	1.50	0.005		0.005
	224.50	226.00	144439	1.50	0.005		0.005
	226.00	227.50	144440	1.50	0.005		0.005
	227.50	229.00	144441	1.50	<0.005		0.001
	229.00	230.50	144443	1.50	<0.005		0.001
	230.50	232.00	144444	1.50	0.010		0.010
	232.00	233.50	144445	1.50	0.013		0.013
	233.50	235.00	144446	1.50	0.019		0.019
	235.00	236.50	144447	1.50	0.014		0.014
	236.50	238.00	144448	1.50	0.011		0.011
	238.00	239.50	144449	1.50	0.018		0.018
	239.50	241.00	144450	1.50	0.009		0.009
	241.00	242.50	144451	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			242.50	244.00	144453	1.50	<0.005		0.001
			244.00	245.50	144454	1.50	0.008		0.008
			245.50	247.00	144455	1.50	0.012		0.012
			247.00	248.50	144456	1.50	0.042		0.042
			248.50	250.00	144457	1.50	0.024		0.024
			250.00	251.50	144458	1.50	<0.005		0.001
			251.50	253.00	144459	1.50	0.016		0.016
			253.00	254.50	144460	1.50	0.008		0.008
			254.50	256.00	144461	1.50	<0.005		0.001
			256.00	257.50	144463	1.50	<0.005		0.001
			257.50	259.00	144464	1.50	<0.005		0.001
			259.00	260.50	144465	1.50	<0.005		0.001
			260.50	262.00	144466	1.50	0.007		0.007
			262.00	263.50	144467	1.50	0.126		0.126
			263.50	265.00	144468	1.50	0.005		0.005
265.00	280.00	BA Basalte Basilte	265.00	266.50	144469	1.50	<0.005		0.001
			266.50	268.00	144470	1.50	<0.005		0.001
			268.00	269.50	144471	1.50	0.005		0.005
			269.50	271.00	144473	1.50	<0.005		0.001
			271.00	272.50	144474	1.50	<0.005		0.001
			272.50	274.00	144475	1.50	0.256		0.256
			274.00	275.50	144476	1.50	0.537		0.537
			275.50	277.00	144477	1.50	0.913		0.913
			277.00	278.50	144478	1.50	0.072		0.072
			278.50	280.00	144479	1.50	0.080		0.080
280.00	298.60	SY Syénite Syénite	280.00	281.50	144480	1.50	0.095		0.095
			281.50	283.00	144481	1.50	0.707		0.707
			283.00	284.50	144483	1.50	3.990	4.28	4.280
			284.50	286.00	144484	1.50	4.980	4.80	4.800
			286.00	287.50	144485	1.50	3.330	3.32	3.320
			287.50	289.00	144486	1.50	4.170	4.20	4.200
			289.00	290.50	144487	1.50	4.620	4.65	4.650
			290.50	292.00	144488	1.50	3.470	3.72	3.720

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
298.60	303.00	BA <b>Basalte</b> Basalte	292.00	293.10	144489	1.10	5.990	6.09	6.090
			293.10	294.50	144490	1.40	1.480		1.480
			294.50	296.00	144491	1.50	3.640	3.87	3.870
			296.00	297.50	144493	1.50	6.720	5.82	5.820
			297.50	298.60	144494	1.10	2.340		2.340
			298.60	300.30	144495	1.70	3.210	3.30	3.300
			300.30	302.00	144496	1.70	0.719		0.719
			302.00	303.00	144497	1.00	1.480		1.480
303.00	310.00	SY <b>Syénite</b> Syénite	303.00	304.50	144498	1.50	9.150	9.68	9.680
			304.50	306.00	144499	1.50	6.490	6.73	6.730
			306.00	307.50	144500	1.50	6.790	7.12	7.120
			307.50	309.00	D010001	1.50	5.350	5.33	5.330
310.00	365.70	BA <b>Basalte</b> Basalte	309.00	310.00	D010003	1.00	0.148		0.148
			310.00	311.50	D010004	1.50	0.025		0.025
			311.50	313.00	D010005	1.50	0.012		0.012
			313.00	314.50	D010006	1.50	0.010		0.010
			314.50	316.00	D010007	1.50	0.005		0.005
			316.00	317.50	D010008	1.50	<0.005		0.001
			317.50	319.00	D010009	1.50	0.005		0.005
			319.00	320.50	D010010	1.50	<0.005		0.001
			320.50	322.00	D010011	1.50	<0.005		0.001
			322.00	323.50	D010013	1.50	<0.005		0.001
			323.50	325.00	D010014	1.50	<0.005		0.001
			325.00	326.50	D010015	1.50	<0.005		0.001
			326.50	328.00	D010016	1.50	<0.005		0.001
			328.00	329.50	D010017	1.50	<0.005		0.001
			329.50	331.00	D010018	1.50	<0.005		0.001
			331.00	332.50	D010019	1.50	<0.005		0.001
			332.50	334.00	D010020	1.50	<0.005		0.001
334.00	335.50	D010021	1.50	<0.005		0.001			
335.50	337.00	D010023	1.50	<0.005		0.001			
337.00	338.50	D010024	1.50	<0.005		0.001			
338.50	340.00	D010025	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			340.00	341.50	D010026	1.50	<0.005		0.001
			341.50	343.00	D010027	1.50	<0.005		0.001
			343.00	344.50	D010028	1.50	0.099		0.099
			344.50	346.00	D010029	1.50	0.608		0.608
			346.00	347.50	D010030	1.50	1.185		1.185
			347.50	349.00	D010031	1.50	0.005		0.005
			349.00	350.50	D010033	1.50	<0.005		0.001
			350.50	352.00	D010034	1.50	<0.005		0.001
			352.00	353.50	D010035	1.50	<0.005		0.001
			353.50	355.00	D010036	1.50	<0.005		0.001
			355.00	356.50	D010037	1.50	<0.005		0.001
			356.50	358.00	D010038	1.50	<0.005		0.001
			358.00	359.50	D010039	1.50	<0.005		0.001
			359.50	361.00	D010040	1.50	<0.005		0.001
			361.00	362.50	D010041	1.50	<0.005		0.001
			362.50	364.10	D010043	1.60	<0.005		0.001
			364.10	365.70	D010044	1.60	<0.005		0.001
365.70	367.40	TU <b>Tuf</b> Tuf	365.70	367.40	D010045	1.70	<0.005		0.001
367.40	380.50	BA <b>Basalte</b> Basalte	367.40	369.00	D010046	1.60	<0.005		0.001
			369.00	370.50	D010047	1.50	<0.005		0.001
			370.50	372.00	D010048	1.50	<0.005		0.001
			372.00	373.50	D010049	1.50	<0.005		0.001
			373.50	375.00	D010050	1.50	<0.005		0.001
			375.00	376.50	D010051	1.50	<0.005		0.001
			376.50	378.00	D010053	1.50	<0.005		0.001
			378.00	379.50	D010054	1.50	<0.005		0.001
			379.50	380.50	D010055	1.00	0.005		0.005
380.50	382.00	TU <b>Tuf</b> Tuf	380.50	382.00	D010056	1.50	<0.005		0.001
382.00	404.00	BA <b>Basalte</b> Basalte	382.00	383.00	D010057	1.00	<0.005		0.001
			383.00	384.50	D010058	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	384.50	386.00	D010059	1.50	<0.005		0.001
	386.00	387.50	D010060	1.50	<0.005		0.001
	387.50	389.00	D010061	1.50	<0.005		0.001
	389.00	390.50	D010063	1.50	<0.005		0.001
	390.50	392.00	D010064	1.50	<0.005		0.001
	392.00	393.50	D010065	1.50	<0.005		0.001
	393.50	395.00	D010066	1.50	<0.005		0.001
	395.00	396.50	D010067	1.50	<0.005		0.001
	396.50	398.00	D010068	1.50	<0.005		0.001
	398.00	399.50	D010069	1.50	<0.005		0.001
	399.50	401.00	D010070	1.50	<0.005		0.001
	401.00	402.50	D010071	1.50	<0.005		0.001
	402.50	404.00	D010072	1.50	<0.005		0.001
404.00	Fin du sondage Nombre d'échantillons : 272 Nombre d'échantillons QAQC : 29 Longueur totale échantillonnée : 402.20						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.40	17.00	144282	144281	1.60	0.047	0.047
29.50	31.00	144292	A3	1.50	0.615	0.615
43.00	44.50	144302	144301	1.50	<0.005	0.001
56.50	58.00	144312	M1	1.50	<0.005	0.001
70.00	71.50	144322	144321	1.50	0.013	0.013
82.50	84.00	144332	B2	1.50	2.520	2.520
94.50	96.00	144342	144341	1.50	0.056	0.056
108.00	109.50	144352	M1	1.50	<0.005	0.001
121.50	123.00	144362	144361	1.50	0.006	0.006
135.00	136.50	144372	C3	1.50	1.320	1.320
148.50	150.00	144382	144381	1.50	0.005	0.005
161.50	163.00	144392	M1	1.50	<0.005	0.001
174.00	175.50	144402	144401	1.50	0.013	0.013
187.50	189.00	144412	D2	1.50	0.832	0.832
201.00	202.50	144422	144421	1.50	<0.005	0.001
214.00	215.50	144432	G2	1.50	4.000	4.030
227.50	229.00	144442	144441	1.50	0.005	0.005
241.00	242.50	144452	M1	1.50	<0.005	0.001
254.50	256.00	144462	144461	1.50	<0.005	0.001
268.00	269.50	144472	H	1.50	0.989	0.989
281.50	283.00	144482	144481	1.50	0.654	0.654
294.50	296.00	144492	M1	1.50	0.006	0.006
307.50	309.00	D010002	D010001	1.50	5.110	5.060
320.50	322.00	D010012	A3	1.50	0.600	0.600
334.00	335.50	D010022	D010021	1.50	<0.005	0.001
347.50	349.00	D010032	M1	1.50	<0.005	0.001
361.00	362.50	D010042	D010041	1.50	<0.005	0.001
375.00	376.50	D010052	B4	1.50	2.700	2.700
387.50	389.00	D010062	D010061	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-116**

Titre minier :

Section :                      630500

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Gilles Kamta

Lot :

Du :                      2010-03-01

Date de description :

Au :                      2010-03-06

Collet

UTM

Azimut :                      180.00°

Plongée :                      -60.00°

Longueur :                      446.00 m

Est                              630 499.9

Nord                              5 374 450.3

Élévation                      302.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	194.10°	-58.00°	Oui
Reflex	5.00	181.20°	-58.00°	Non
Reflex	8.00	181.90°	-58.00°	Non
Reflex	11.00	181.70°	-58.10°	Non
Reflex	14.00	182.40°	-58.00°	Non
Reflex	17.00	183.40°	-57.90°	Non
Reflex	20.00	182.60°	-58.00°	Non
Reflex	23.00	180.40°	-57.90°	Oui
Reflex	26.00	183.00°	-57.90°	Non
Reflex	29.00	183.00°	-57.70°	Non
Reflex	32.00	181.60°	-57.80°	Non
Reflex	35.00	182.60°	-57.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	182.30°	-57.90°	Non
Reflex	41.00	180.60°	-57.70°	Oui
Reflex	44.00	181.50°	-57.70°	Non
Reflex	47.00	180.90°	-57.40°	Non
Reflex	50.00	182.70°	-57.60°	Non
Reflex	53.00	183.10°	-57.60°	Non
Reflex	56.00	182.20°	-57.70°	Non
Reflex	59.00	181.70°	-57.60°	Non
Reflex	62.00	181.80°	-57.40°	Non
Reflex	65.00	183.50°	-57.50°	Oui
Reflex	68.00	182.70°	-57.60°	Non
Reflex	71.00	181.60°	-57.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	181.20°	-57.20°	Non	Reflex	173.00	181.60°	-56.90°	Non
Reflex	77.00	181.00°	-57.10°	Non	Reflex	176.00	181.40°	-56.90°	Non
Reflex	80.00	180.90°	-57.10°	Non	Reflex	179.00	181.50°	-57.00°	Non
Reflex	83.00	178.40°	-57.00°	Oui	Reflex	182.00	181.60°	-56.90°	Non
Reflex	86.00	181.40°	-56.90°	Non	Reflex	185.00	183.90°	-57.00°	Non
Reflex	89.00	181.40°	-56.90°	Non	Reflex	188.00	182.50°	-56.80°	Non
Reflex	92.00	181.80°	-56.80°	Non	Reflex	191.00	182.30°	-56.90°	Non
Reflex	95.00	181.90°	-56.90°	Non	Reflex	194.00	182.40°	-56.90°	Non
Reflex	98.00	180.60°	-56.80°	Non	Reflex	197.00	182.00°	-56.90°	Non
Reflex	101.00	181.10°	-56.80°	Non	Reflex	200.00	182.90°	-56.90°	Non
Reflex	104.00	180.70°	-57.00°	Non	Reflex	203.00	183.10°	-56.80°	Non
Reflex	107.00	179.40°	-56.90°	Non	Reflex	206.00	183.70°	-56.80°	Non
Reflex	110.00	180.10°	-56.90°	Non	Reflex	209.00	183.80°	-56.80°	Non
Reflex	113.00	180.30°	-56.90°	Non	Reflex	212.00	182.80°	-56.80°	Non
Reflex	116.00	179.20°	-57.00°	Non	Reflex	215.00	183.80°	-56.90°	Non
Reflex	119.00	181.20°	-56.80°	Non	Reflex	218.00	182.70°	-56.90°	Non
Reflex	122.00	181.30°	-57.10°	Non	Reflex	221.00	181.90°	-56.70°	Non
Reflex	125.00	181.00°	-56.80°	Non	Reflex	224.00	182.30°	-56.80°	Non
Reflex	128.00	180.40°	-56.90°	Non	Reflex	227.00	180.10°	-56.80°	Non
Reflex	131.00	181.00°	-56.90°	Non	Reflex	230.00	181.20°	-56.80°	Non
Reflex	134.00	181.10°	-56.90°	Non	Reflex	233.00	183.60°	-56.90°	Oui
Reflex	137.00	182.30°	-57.10°	Non	Reflex	236.00	182.80°	-56.80°	Non
Reflex	140.00	181.40°	-56.80°	Non	Reflex	239.00	181.50°	-56.80°	Non
Reflex	143.00	181.80°	-56.90°	Non	Reflex	242.00	182.40°	-56.90°	Non
Reflex	146.00	180.50°	-56.90°	Non	Reflex	245.00	180.80°	-56.80°	Non
Reflex	149.00	180.90°	-56.90°	Non	Reflex	248.00	183.20°	-56.90°	Non
Reflex	152.00	181.20°	-56.90°	Non	Reflex	251.00	183.20°	-56.80°	Non
Reflex	155.00	180.60°	-56.90°	Non	Reflex	254.00	182.80°	-56.90°	Non
Reflex	158.00	177.50°	-56.90°	Oui	Reflex	257.00	183.20°	-56.90°	Non
Reflex	161.00	179.20°	-56.90°	Non	Reflex	260.00	183.40°	-57.00°	Non
Reflex	164.00	181.50°	-56.90°	Non	Reflex	263.00	183.00°	-56.80°	Non
Reflex	167.00	181.30°	-57.00°	Non	Reflex	266.00	182.40°	-56.80°	Non
Reflex	170.00	181.80°	-57.00°	Non	Reflex	269.00	184.30°	-56.90°	Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	182.70°	-56.80°	Non	Reflex	371.00	184.00°	-56.10°	Non
Reflex	275.00	183.50°	-56.80°	Non	Reflex	374.00	184.60°	-55.90°	Non
Reflex	278.00	183.70°	-56.80°	Non	Reflex	377.00	184.20°	-56.00°	Non
Reflex	281.00	183.60°	-56.70°	Non	Reflex	380.00	183.60°	-55.90°	Non
Reflex	284.00	182.70°	-56.60°	Non	Reflex	383.00	184.70°	-55.80°	Non
Reflex	287.00	182.60°	-56.70°	Non	Reflex	386.00	184.70°	-55.90°	Non
Reflex	290.00	183.50°	-56.80°	Non	Reflex	389.00	183.50°	-55.70°	Non
Reflex	293.00	182.80°	-56.80°	Non	Reflex	392.00	185.90°	-55.70°	Non
Reflex	296.00	183.20°	-56.80°	Non	Reflex	395.00	185.30°	-55.80°	Non
Reflex	299.00	183.00°	-56.70°	Non	Reflex	398.00	184.90°	-55.70°	Non
Reflex	302.00	183.00°	-56.60°	Non	Reflex	401.00	185.00°	-55.70°	Non
Reflex	305.00	182.70°	-56.70°	Non	Reflex	404.00	184.70°	-55.70°	Non
Reflex	308.00	183.00°	-56.50°	Non	Reflex	407.00	185.40°	-55.50°	Non
Reflex	311.00	183.10°	-56.60°	Non	Reflex	410.00	185.20°	-55.70°	Non
Reflex	314.00	182.70°	-56.70°	Non	Reflex	413.00	185.90°	-55.80°	Non
Reflex	317.00	183.20°	-56.60°	Non	Reflex	416.00	186.00°	-55.60°	Non
Reflex	320.00	184.10°	-56.50°	Non	Reflex	419.00	184.90°	-55.60°	Non
Reflex	323.00	184.40°	-56.70°	Non	Reflex	422.00	185.60°	-55.60°	Non
Reflex	326.00	187.00°	-56.50°	Oui	Reflex	425.00	186.60°	-55.40°	Non
Reflex	329.00	185.80°	-56.50°	Non	Reflex	428.00	186.20°	-55.40°	Non
Reflex	332.00	185.90°	-56.40°	Non	Reflex	431.00	185.50°	-55.50°	Non
Reflex	335.00	185.50°	-56.30°	Non	Reflex	434.00	185.50°	-55.30°	Non
Reflex	338.00	184.40°	-56.20°	Non	Reflex	437.00	186.00°	-55.50°	Non
Reflex	341.00	183.20°	-56.30°	Non	Reflex	440.00	185.30°	-55.30°	Non
Reflex	344.00	183.80°	-56.20°	Non	Reflex	443.00	185.30°	-55.10°	Non
Reflex	347.00	183.70°	-56.10°	Non					
Reflex	350.00	185.30°	-56.20°	Non					
Reflex	353.00	183.60°	-56.10°	Non					
Reflex	356.00	184.10°	-56.10°	Non					
Reflex	359.00	182.70°	-56.10°	Oui					
Reflex	362.00	185.00°	-55.90°	Non					
Reflex	365.00	183.70°	-56.10°	Non					
Reflex	368.00	183.40°	-56.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.00	MT Mort-terrain MT						
2.00	433.70	SY Syénite Syénite	2.00	3.50	D000001	1.50	<0.005	0.001
			3.50	5.00	D000002	1.50	<0.005	0.001
			5.00	6.50	D000003	1.50	<0.005	0.001
			6.50	8.00	D000004	1.50	<0.005	0.001
			8.00	9.50	D000005	1.50	<0.005	0.001
			9.50	11.00	D000006	1.50	<0.005	0.001
			11.00	12.50	D000007	1.50	<0.005	0.001
			12.50	14.00	D000008	1.50	<0.005	0.001
			14.00	15.50	D000009	1.50	0.014	0.014
			15.50	17.00	D000011	1.50	0.051	0.051
			17.00	18.50	D000012	1.50	<0.005	0.001
			18.50	20.00	D000013	1.50	0.029	0.029
			20.00	21.50	D000014	1.50	<0.005	0.001
			21.50	23.00	D000015	1.50	<0.005	0.001
			23.00	24.50	D000016	1.50	0.017	0.017
			24.50	26.00	D000017	1.50	0.185	0.185
			26.00	27.50	D000018	1.50	0.009	0.009
			27.50	29.00	D000019	1.50	0.005	0.005
			29.00	30.50	D000020	1.50	0.013	0.013
			30.50	32.00	D000022	1.50	0.066	0.066
			32.00	33.50	D000023	1.50	0.633	0.633
			33.50	35.00	D000024	1.50	0.023	0.023
			35.00	36.50	D000025	1.50	0.419	0.419
			36.50	38.00	D000026	1.50	0.054	0.054
			38.00	39.50	D000027	1.50	0.461	0.461
			39.50	41.00	D000028	1.50	0.683	0.683
			41.00	42.50	D000029	1.50	0.151	0.151
			42.50	44.00	D000031	1.50	0.015	0.015
			44.00	45.50	D000032	1.50	0.064	0.064
			45.50	47.00	D000033	1.50	0.024	0.024
			47.00	48.40	D000034	1.40	0.036	0.036

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.40	49.40	D000035	1.00	0.082		0.082
	49.40	50.40	D000036	1.00	0.007		0.007
	50.40	52.00	D000037	1.60	0.015		0.015
	52.00	53.00	D000038	1.00	0.009		0.009
	53.00	54.50	D000039	1.50	0.171		0.171
	54.50	55.70	D000040	1.20	0.112		0.112
	55.70	57.00	D000042	1.30	0.005		0.005
	57.00	58.50	D000043	1.50	<0.005		0.001
	58.50	60.00	D000044	1.50	0.014		0.014
	60.00	61.50	D000045	1.50	0.005		0.005
	61.50	63.00	D000046	1.50	0.006		0.006
	63.00	64.50	D000047	1.50	0.005		0.005
	64.50	66.00	D000048	1.50	0.005		0.005
	66.00	67.50	D000049	1.50	<0.005		0.001
	67.50	69.00	D000051	1.50	0.005		0.005
	69.00	70.50	D000052	1.50	0.005		0.005
	70.50	72.00	D000053	1.50	0.005		0.005
	72.00	73.20	D000054	1.20	<0.005		0.001
	73.20	74.30	D000055	1.10	0.009		0.009
	74.30	75.50	D000056	1.20	0.095		0.095
	75.50	77.00	D000057	1.50	0.062		0.062
	77.00	78.00	D000058	1.00	0.168		0.168
	78.00	79.00	D000059	1.00	0.105		0.105
	79.00	80.00	D000060	1.00	0.094		0.094
	80.00	81.00	D000062	1.00	0.110		0.110
	81.00	82.50	D000063	1.50	0.642		0.642
	82.50	84.00	D000064	1.50	0.024		0.024
	84.00	85.50	D000065	1.50	0.031		0.031
	85.50	86.80	D000066	1.30	0.276		0.276
	86.80	88.50	D000067	1.70	0.008		0.008
	88.50	90.00	D000068	1.50	0.005		0.005
	90.00	91.50	D000069	1.50	0.173		0.173
	91.50	93.00	D000071	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	93.00	94.50	D000072	1.50	0.010		0.010
	94.50	96.00	D000073	1.50	<0.005		0.001
	96.00	97.50	D000074	1.50	<0.005		0.001
	97.50	99.00	D000075	1.50	<0.005		0.001
	99.00	100.50	D000076	1.50	<0.005		0.001
	100.50	102.00	D000077	1.50	<0.005		0.001
	102.00	103.50	D000078	1.50	<0.005		0.001
	103.50	105.00	D000079	1.50	<0.005		0.001
	105.00	106.50	D000080	1.50	<0.005		0.001
	106.50	108.00	D000082	1.50	0.071		0.071
	108.00	109.50	D000083	1.50	0.086		0.086
	109.50	111.00	D000084	1.50	0.018		0.018
	111.00	112.50	D000085	1.50	0.014		0.014
	112.50	114.00	D000086	1.50	0.058		0.058
	114.00	115.50	D000087	1.50	<0.005		0.001
	115.50	117.00	D000088	1.50	<0.005		0.001
	117.00	118.50	D000089	1.50	0.018		0.018
	118.50	120.00	D000091	1.50	0.011		0.011
	120.00	121.00	D000092	1.00	<0.005		0.001
	121.00	122.00	D000093	1.00	0.174		0.174
	122.00	123.50	D000094	1.50	0.085		0.085
	123.50	125.00	D000095	1.50	<0.005		0.001
	125.00	126.50	D000096	1.50	0.007		0.007
	126.50	128.00	D000097	1.50	0.005		0.005
	128.00	129.00	D000098	1.00	0.017		0.017
	129.00	130.00	D000099	1.00	0.054		0.054
	130.00	131.50	D000100	1.50	<0.005		0.001
	131.50	133.00	D000102	1.50	0.005		0.005
	133.00	134.50	D000103	1.50	<0.005		0.001
	134.50	136.00	D000104	1.50	<0.005		0.001
	136.00	137.50	D000105	1.50	<0.005		0.001
	137.50	139.00	D000106	1.50	<0.005		0.001
	139.00	140.50	D000107	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	140.50	142.00	D000108	1.50	<0.005		0.001
	142.00	143.50	D000109	1.50	<0.005		0.001
	143.50	145.00	D000111	1.50	<0.005		0.001
	145.00	146.50	D000112	1.50	<0.005		0.001
	146.50	148.00	D000113	1.50	<0.005		0.001
	148.00	149.50	D000114	1.50	<0.005		0.001
	149.50	151.00	D000115	1.50	<0.005		0.001
	151.00	152.50	D000116	1.50	<0.005		0.001
	152.50	154.00	D000117	1.50	<0.005		0.001
	154.00	155.50	D000118	1.50	<0.005		0.001
	155.50	157.00	D000119	1.50	<0.005		0.001
	157.00	158.50	D000120	1.50	<0.005		0.001
	158.50	160.00	D000122	1.50	<0.005		0.001
	160.00	161.50	D000123	1.50	<0.005		0.001
	161.50	163.00	D000124	1.50	<0.005		0.001
	163.00	164.00	D000125	1.00	<0.005		0.001
	164.00	164.80	D000126	0.80	0.013		0.013
	164.80	166.20	D000127	1.40	0.026		0.026
	166.20	167.20	D000128	1.00	0.087		0.087
	167.20	168.20	D000129	1.00	0.151		0.151
	168.20	169.40	D000131	1.20	<0.005		0.001
	169.40	171.00	D000132	1.60	<0.005		0.001
	171.00	172.50	D000133	1.50	<0.005		0.001
	172.50	174.00	D000134	1.50	<0.005		0.001
	174.00	175.50	D000135	1.50	<0.005		0.001
	175.50	177.00	D000136	1.50	<0.005		0.001
	177.00	178.50	D000137	1.50	<0.005		0.001
	178.50	180.00	D000138	1.50	<0.005		0.001
	180.00	181.50	D000139	1.50	<0.005		0.001
	181.50	183.00	D000140	1.50	<0.005		0.001
	183.00	184.50	D000142	1.50	<0.005		0.001
	184.50	186.00	D000143	1.50	<0.005		0.001
	186.00	187.50	D000144	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	187.50	189.00	D000145	1.50	0.005		0.005
	189.00	190.50	D000146	1.50	<0.005		0.001
	190.50	192.00	D000147	1.50	0.007		0.007
	192.00	193.50	D000148	1.50	0.005		0.005
	193.50	195.00	D000149	1.50	0.029		0.029
	195.00	196.50	D000151	1.50	<0.005		0.001
	196.50	198.00	D000152	1.50	0.005		0.005
	198.00	199.50	D000153	1.50	0.008		0.008
	199.50	201.00	D000154	1.50	0.021		0.021
	201.00	202.50	D000155	1.50	0.008		0.008
	202.50	204.00	D000156	1.50	0.042		0.042
	204.00	205.50	D000157	1.50	<0.005		0.001
	205.50	207.00	D000158	1.50	0.008		0.008
	207.00	208.50	D000159	1.50	<0.005		0.001
	208.50	210.00	D000160	1.50	<0.005		0.001
	210.00	211.50	D000162	1.50	0.036		0.036
	211.50	213.00	D000163	1.50	0.010		0.010
	213.00	214.50	D000164	1.50	<0.005		0.001
	214.50	216.00	D000165	1.50	<0.005		0.001
	216.00	217.50	D000166	1.50	<0.005		0.001
	217.50	219.00	D000167	1.50	<0.005		0.001
	219.00	220.50	D000168	1.50	<0.005		0.001
	220.50	222.00	D000169	1.50	0.010		0.010
	222.00	223.50	D000171	1.50	<0.005		0.001
	223.50	225.00	D000172	1.50	<0.005		0.001
	225.00	226.50	D000173	1.50	0.005		0.005
	226.50	228.00	D000174	1.50	<0.005		0.001
	228.00	229.50	D000175	1.50	0.023		0.023
	229.50	231.00	D000176	1.50	0.086		0.086
	231.00	232.50	D000177	1.50	0.035		0.035
	232.50	234.00	D000178	1.50	0.021		0.021
	234.00	235.50	D000179	1.50	0.006		0.006
	235.50	237.00	D000180	1.50	0.056		0.056

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	237.00	238.50	D000182	1.50	0.013		0.013
	238.50	240.00	D000183	1.50	0.067		0.067
	240.00	241.50	D000184	1.50	<0.005		0.001
	241.50	243.00	D000185	1.50	<0.005		0.001
	243.00	244.50	D000186	1.50	<0.005		0.001
	244.50	246.00	D000187	1.50	0.057		0.057
	246.00	247.50	D000188	1.50	0.008		0.008
	247.50	249.00	D000189	1.50	0.032		0.032
	249.00	250.50	D000191	1.50	<0.005		0.001
	250.50	252.00	D000192	1.50	<0.005		0.001
	252.00	253.50	D000193	1.50	<0.005		0.001
	253.50	255.00	D000194	1.50	0.006		0.006
	255.00	256.50	D000195	1.50	0.006		0.006
	256.50	258.00	D000196	1.50	<0.005		0.001
	258.00	259.50	D000197	1.50	<0.005		0.001
	259.50	261.00	D000198	1.50	<0.005		0.001
	261.00	262.50	D000199	1.50	<0.005		0.001
	262.50	264.00	D000200	1.50	0.011		0.011
	264.00	265.50	D000202	1.50	0.132		0.132
	265.50	267.00	D000203	1.50	0.008		0.008
	267.00	268.50	D000204	1.50	0.006		0.006
	268.50	270.00	D000205	1.50	<0.005		0.001
	270.00	271.50	D000206	1.50	<0.005		0.001
	271.50	273.00	D000207	1.50	<0.005		0.001
	273.00	274.50	D000208	1.50	<0.005		0.001
	274.50	276.00	D000209	1.50	0.008		0.008
	276.00	277.50	D000211	1.50	0.006		0.006
	277.50	279.00	D000212	1.50	0.054		0.054
	279.00	280.50	D000213	1.50	0.115		0.115
	280.50	281.70	D000214	1.20	<0.005		0.001
	281.70	282.80	D000215	1.10	0.027		0.027
	282.80	283.80	D000216	1.00	0.008		0.008
	283.80	284.80	D000217	1.00	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	284.80	286.00	D000218	1.20	<0.005		0.001
	286.00	287.50	D000219	1.50	<0.005		0.001
	287.50	289.00	D000220	1.50	<0.005		0.001
	289.00	290.50	D000222	1.50	0.033		0.033
	290.50	292.00	D000223	1.50	<0.005		0.001
	292.00	293.50	D000224	1.50	<0.005		0.001
	293.50	295.00	D000225	1.50	<0.005		0.001
	295.00	296.50	D000226	1.50	<0.005		0.001
	296.50	298.00	D000227	1.50	<0.005		0.001
	298.00	299.50	D000228	1.50	<0.005		0.001
	299.50	301.00	D000229	1.50	<0.005		0.001
	301.00	302.50	D000231	1.50	<0.005		0.001
	302.50	304.00	D000232	1.50	0.009		0.009
	304.00	305.50	D000233	1.50	<0.005		0.001
	305.50	307.00	D000234	1.50	<0.005		0.001
	307.00	308.50	D000235	1.50	<0.005		0.001
	308.50	310.00	D000236	1.50	<0.005		0.001
	310.00	311.50	D000237	1.50	<0.005		0.001
	311.50	313.00	D000238	1.50	<0.005		0.001
	313.00	314.50	D000239	1.50	<0.005		0.001
	314.50	316.00	D000240	1.50	<0.005		0.001
	316.00	317.50	D000242	1.50	<0.005		0.001
	317.50	319.00	D000243	1.50	<0.005		0.001
	319.00	320.50	D000244	1.50	<0.005		0.001
	320.50	322.00	D000245	1.50	<0.005		0.001
	322.00	323.50	D000246	1.50	<0.005		0.001
	323.50	325.00	D000247	1.50	<0.005		0.001
	325.00	326.00	D000248	1.00	<0.005		0.001
	326.00	327.00	D000249	1.00	<0.005		0.001
	327.00	328.50	D000251	1.50	<0.005		0.001
	328.50	330.00	D000252	1.50	0.017		0.017
	330.00	331.50	D000253	1.50	0.036		0.036
	331.50	333.00	D000254	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	333.00	334.50	D000255	1.50	0.038		0.038
	334.50	336.00	D000256	1.50	0.006		0.006
	336.00	337.50	D000257	1.50	<0.005		0.001
	337.50	339.00	D000258	1.50	<0.005		0.001
	339.00	340.50	D000259	1.50	0.006		0.006
	340.50	342.00	D000261	1.50	<0.005		0.001
	342.00	343.50	D000262	1.50	0.007		0.007
	343.50	345.00	D000263	1.50	0.016		0.016
	345.00	346.50	D000264	1.50	0.006		0.006
	346.50	348.00	D000265	1.50	<0.005		0.001
	348.00	349.00	D000266	1.00	0.006		0.006
	349.00	350.10	D000267	1.10	0.010		0.010
	350.10	351.50	D000268	1.40	0.017		0.017
	351.50	353.00	D000269	1.50	0.152		0.152
	353.00	354.50	D000271	1.50	0.017		0.017
	354.50	356.00	D000272	1.50	0.063		0.063
	356.00	357.50	D000273	1.50	0.024		0.024
	357.50	359.00	D000274	1.50	0.022		0.022
	359.00	360.50	D000275	1.50	0.062		0.062
	360.50	362.00	D000276	1.50	0.022		0.022
	362.00	363.50	D000277	1.50	0.142		0.142
	363.50	365.00	D000278	1.50	0.016		0.016
	365.00	366.50	D000279	1.50	0.366		0.366
	366.50	368.00	D000281	1.50	0.277		0.277
	368.00	369.50	D000282	1.50	0.015		0.015
	369.50	371.00	D000283	1.50	0.047		0.047
	371.00	372.50	D000284	1.50	0.015		0.015
	372.50	374.00	D000285	1.50	0.059		0.059
	374.00	375.50	D000286	1.50	0.046		0.046
	375.50	377.00	D000287	1.50	0.029		0.029
	377.00	378.50	D000288	1.50	0.567		0.567
	378.50	380.00	D000289	1.50	0.048		0.048
	380.00	381.50	D000291	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	381.50	383.00	D000292	1.50	<0.005		0.001
	383.00	384.50	D000293	1.50	0.019		0.019
	384.50	386.00	D000294	1.50	0.007		0.007
	386.00	387.50	D000295	1.50	0.009		0.009
	387.50	389.00	D000296	1.50	0.042		0.042
	389.00	390.50	D000297	1.50	0.009		0.009
	390.50	392.00	D000298	1.50	0.013		0.013
	392.00	393.50	D000299	1.50	0.109		0.109
	393.50	395.00	D000301	1.50	0.008		0.008
	395.00	396.50	D000302	1.50	0.006		0.006
	396.50	398.00	D000303	1.50	<0.005		0.001
	398.00	399.50	D000304	1.50	0.029		0.029
	399.50	401.00	D000305	1.50	0.043		0.043
	401.00	402.50	D000306	1.50	0.008		0.008
	402.50	404.00	D000307	1.50	0.052		0.052
	404.00	405.50	D000308	1.50	0.007		0.007
	405.50	407.00	D000309	1.50	0.021		0.021
	407.00	408.50	D000311	1.50	0.030		0.030
	408.50	410.00	D000312	1.50	0.048		0.048
	410.00	411.50	D000313	1.50	0.050		0.050
	411.50	413.00	D000314	1.50	0.077		0.077
	413.00	414.50	D000315	1.50	0.011		0.011
	414.50	416.00	D000316	1.50	<0.005		0.001
	416.00	417.50	D000317	1.50	<0.005		0.001
	417.50	419.00	D000318	1.50	<0.005		0.001
	419.00	420.50	D000319	1.50	0.011		0.011
	420.50	422.00	D000321	1.50	0.008		0.008
	422.00	423.50	D000322	1.50	0.023		0.023
	423.50	425.00	D000323	1.50	0.020		0.020
	425.00	426.50	D000324	1.50	0.170		0.170
	426.50	428.00	D000325	1.50	<0.005		0.001
	428.00	429.50	D000326	1.50	0.135		0.135
	429.50	431.00	D000327	1.50	0.165		0.165

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
433.70	438.00	UM <b>Ultramafique</b> Ultramafique	431.00	432.50	D000328	1.50	0.039		0.039
			432.50	433.70	D000329	1.20	2.070		2.070
			433.70	435.00	D000331	1.30	0.381		0.381
			435.00	436.50	D000332	1.50	0.032		0.032
			436.50	438.00	D000333	1.50	<0.005		0.001
438.00	446.00	SY <b>Syénite</b> Syénite	438.00	439.60	D000334	1.60	0.179		0.179
			439.60	441.00	D000335	1.40	0.005		0.005
			441.00	442.50	D000336	1.50	<0.005		0.001
			442.50	444.00	D000337	1.50	0.005		0.005
			444.00	445.00	D000338	1.00	<0.005		0.001
			445.00	446.00	D000339	1.00	<0.005		0.001
446.00	Fin du sondage Nombre d'échantillons : 306 Nombre d'échantillons QAQC : 33 Longueur totale échantillonnée : 444.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.50	15.50	D000010	D000009	0.00	0.018	0.018
30.50	30.50	D000021	A3	0.00	0.620	0.620
42.50	42.50	D000030	D000029	0.00	0.157	0.157
55.70	55.70	D000041	B4	0.00	2.660	2.660
67.50	67.50	D000050	D000049	0.00	<0.005	0.001
80.00	80.00	D000061	M1	0.00	<0.005	0.001
91.50	91.50	D000070	D000069	0.00	0.153	0.153
106.50	106.50	D000081	C3	0.00	1.400	1.400
118.50	118.50	D000090	D000089	0.00	0.027	0.027
131.50	131.50	D000101	G2	0.00	4.080	4.060
143.50	143.50	D000110	D000109	0.00	<0.005	0.001
158.50	158.50	D000121	M1	0.00	<0.005	0.001
168.20	168.20	D000130	D000129	0.00	0.205	0.205
183.00	183.00	D000141	D2	0.00	0.904	0.904
195.00	195.00	D000150	D000149	0.00	0.007	0.007
210.00	210.00	D000161	G2	0.00	4.150	4.220
222.00	222.00	D000170	D000169	0.00	<0.005	0.001
237.00	237.00	D000181	M1	0.00	<0.005	0.001
249.00	249.00	D000190	D000189	0.00	0.036	0.036
264.00	264.00	D000201	H	0.00	1.025	1.025
276.00	276.00	D000210	D000209	0.00	<0.005	0.001
289.00	289.00	D000221	F2	0.00	8.660	8.260
301.00	301.00	D000230	D000229	0.00	<0.005	0.001
316.00	316.00	D000241	M1	0.00	<0.005	0.001
327.00	327.00	D000250	D000249	0.00	<0.005	0.001
340.50	340.50	D000260	A3	0.00	0.620	0.620
353.00	353.00	D000270	D000269	0.00	0.152	0.152
366.50	366.50	D000280	B4	0.00	2.680	2.680
380.00	380.00	D000290	D000289	0.00	0.041	0.041
393.50	393.50	D000300	M1	0.00	<0.005	0.001
407.00	407.00	D000310	D000309	0.00	0.024	0.024
420.50	420.50	D000320	C3	0.00	1.385	1.385
433.70	433.70	D000330	D000329	0.00	2.190	2.190

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-117**

Titre minier :

Section :                      630100

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles Kamta

Lot :

Du :                              2010-02-22

Date de description :

Au :                              2010-02-27

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      395.00 m

Est	630 099.9
Nord	5 374 400.8
Élévation	283.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	328.60°	-60.50°	Oui
Reflex	5.00	319.80°	-60.50°	Oui
Reflex	8.00	347.80°	-60.60°	Oui
Reflex	11.00	325.70°	-60.40°	Oui
Reflex	14.00	3.00°	-60.40°	Oui
Reflex	17.00	346.00°	-60.30°	Oui
Reflex	20.00	48.40°	-60.30°	Oui
Reflex	23.00	358.40°	-60.50°	Non
Reflex	26.00	357.90°	-60.40°	Non
Reflex	29.00	1.00°	-60.30°	Non
Reflex	32.00	1.00°	-60.20°	Non
Reflex	35.00	1.10°	-60.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.90°	-60.20°	Non
Reflex	41.00	1.40°	-60.10°	Non
Reflex	44.00	2.10°	-60.20°	Non
Reflex	47.00	3.60°	-60.10°	Oui
Reflex	50.00	0.70°	-60.10°	Oui
Reflex	53.00	2.40°	-60.10°	Non
Reflex	56.00	0.20°	-60.10°	Oui
Reflex	59.00	1.20°	-60.10°	Oui
Reflex	62.00	2.10°	-60.10°	Non
Reflex	65.00	4.20°	-62.30°	Oui
Reflex	68.00	1.80°	-60.10°	Non
Reflex	71.00	2.20°	-60.10°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.50°	-60.10°	Non	Reflex	173.00	1.80°	-59.70°	Non
Reflex	77.00	0.90°	-60.10°	Non	Reflex	176.00	0.90°	-59.70°	Non
Reflex	80.00	1.00°	-60.10°	Non	Reflex	179.00	2.90°	-59.70°	Non
Reflex	83.00	0.70°	-60.10°	Non	Reflex	182.00	2.80°	-59.60°	Non
Reflex	86.00	1.90°	-60.10°	Non	Reflex	185.00	1.70°	-59.60°	Oui
Reflex	89.00	1.70°	-60.10°	Non	Reflex	188.00	4.00°	-59.60°	Non
Reflex	92.00	2.20°	-60.10°	Non	Reflex	191.00	4.40°	-59.50°	Non
Reflex	95.00	2.60°	-60.10°	Non	Reflex	194.00	2.30°	-59.40°	Oui
Reflex	98.00	2.70°	-60.10°	Non	Reflex	197.00	3.50°	-59.40°	Non
Reflex	101.00	2.80°	-60.20°	Non	Reflex	200.00	2.40°	-59.30°	Non
Reflex	104.00	3.20°	-60.20°	Non	Reflex	203.00	1.90°	-59.30°	Non
Reflex	107.00	3.10°	-60.10°	Non	Reflex	206.00	2.30°	-59.30°	Non
Reflex	110.00	3.10°	-60.00°	Non	Reflex	209.00	2.40°	-59.20°	Non
Reflex	113.00	3.20°	-60.10°	Non	Reflex	212.00	2.40°	-59.20°	Non
Reflex	116.00	3.90°	-60.10°	Non	Reflex	215.00	2.40°	-59.20°	Non
Reflex	119.00	4.00°	-60.10°	Non	Reflex	218.00	2.40°	-59.10°	Non
Reflex	122.00	3.90°	-60.10°	Non	Reflex	221.00	2.50°	-59.10°	Non
Reflex	125.00	3.70°	-60.10°	Non	Reflex	224.00	2.60°	-59.10°	Non
Reflex	128.00	3.60°	-60.10°	Non	Reflex	227.00	2.70°	-59.10°	Non
Reflex	131.00	3.00°	-60.10°	Non	Reflex	230.00	2.60°	-58.90°	Non
Reflex	134.00	3.20°	-60.00°	Non	Reflex	233.00	2.50°	-58.90°	Non
Reflex	137.00	4.30°	-60.00°	Non	Reflex	236.00	2.60°	-58.80°	Non
Reflex	140.00	3.30°	-59.90°	Non	Reflex	239.00	2.80°	-58.80°	Non
Reflex	143.00	4.10°	-60.00°	Non	Reflex	242.00	3.00°	-58.80°	Non
Reflex	146.00	3.50°	-59.90°	Non	Reflex	245.00	3.20°	-58.80°	Non
Reflex	149.00	2.00°	-59.90°	Oui	Reflex	248.00	3.20°	-58.70°	Non
Reflex	152.00	3.70°	-59.80°	Non	Reflex	251.00	3.20°	-58.60°	Non
Reflex	155.00	2.30°	-59.80°	Oui	Reflex	254.00	3.20°	-58.50°	Non
Reflex	158.00	4.40°	-59.80°	Non	Reflex	257.00	3.20°	-58.50°	Non
Reflex	161.00	2.90°	-59.70°	Non	Reflex	260.00	3.10°	-58.50°	Non
Reflex	164.00	2.50°	-59.70°	Non	Reflex	263.00	3.10°	-58.40°	Non
Reflex	167.00	2.60°	-59.70°	Non	Reflex	266.00	3.00°	-58.50°	Non
Reflex	170.00	1.60°	-59.70°	Non	Reflex	269.00	2.70°	-58.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	2.70°	-58.30°	Non	Reflex	371.00	1.00°	-55.70°	Non
Reflex	275.00	2.80°	-58.30°	Non	Reflex	374.00	1.00°	-55.70°	Non
Reflex	278.00	2.90°	-58.10°	Non	Reflex	377.00	0.90°	-55.70°	Non
Reflex	281.00	2.70°	-58.00°	Non	Reflex	380.00	0.80°	-55.60°	Non
Reflex	284.00	2.60°	-57.80°	Non	Reflex	383.00	0.70°	-55.60°	Non
Reflex	287.00	2.50°	-57.70°	Non	Reflex	386.00	0.50°	-55.60°	Non
Reflex	290.00	2.40°	-57.60°	Non	Reflex	389.00	0.40°	-55.60°	Non
Reflex	293.00	2.40°	-57.40°	Non	Reflex	392.00	0.70°	-55.60°	Non
Reflex	296.00	2.30°	-57.20°	Non	Reflex	395.00	0.60°	-55.50°	Non
Reflex	299.00	2.10°	-57.10°	Non					
Reflex	302.00	1.90°	-56.80°	Non					
Reflex	305.00	1.60°	-56.60°	Non					
Reflex	308.00	1.50°	-56.60°	Non					
Reflex	311.00	1.50°	-56.50°	Non					
Reflex	314.00	1.60°	-56.50°	Non					
Reflex	317.00	1.50°	-56.40°	Non					
Reflex	320.00	1.60°	-56.30°	Non					
Reflex	323.00	1.70°	-56.20°	Non					
Reflex	326.00	1.50°	-56.20°	Non					
Reflex	329.00	1.40°	-56.20°	Non					
Reflex	332.00	1.40°	-56.10°	Non					
Reflex	335.00	1.40°	-56.10°	Non					
Reflex	338.00	1.40°	-56.00°	Non					
Reflex	341.00	1.40°	-56.00°	Non					
Reflex	344.00	1.30°	-55.90°	Non					
Reflex	347.00	1.30°	-56.00°	Non					
Reflex	350.00	1.20°	-55.90°	Non					
Reflex	353.00	1.20°	-55.90°	Non					
Reflex	356.00	1.30°	-55.80°	Non					
Reflex	359.00	1.20°	-55.70°	Non					
Reflex	362.00	1.10°	-55.70°	Non					
Reflex	365.00	1.10°	-55.70°	Non					
Reflex	368.00	1.00°	-55.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	26.50	MT <b>Mort-terrain</b> MT						
26.50	41.60	SY <b>Syénite</b> Syénite	26.50	28.00	D000340	1.50	0.007	0.007
			28.00	29.50	D000341	1.50	0.480	0.480
			29.50	31.00	D000342	1.50	0.047	0.047
			31.00	32.50	D000343	1.50	2.020	2.020
			32.50	34.00	D000344	1.50	0.904	0.904
			34.00	35.50	D000345	1.50	1.245	1.245
			35.50	37.00	D000346	1.50	1.165	1.165
			37.00	38.50	D000347	1.50	1.110	1.110
			38.50	40.00	D000348	1.50	0.554	0.554
			40.00	41.60	D000350	1.60	1.990	1.990
41.60	42.30	LOST <b>LOST</b> Carottes perdues						
42.30	191.30	SY <b>Syénite</b> Syénite	42.30	43.50	D000351	1.20	2.590	2.590
			43.50	45.00	D000352	1.50	2.480	2.480
			45.00	46.50	D000353	1.50	1.875	1.875
			46.50	48.00	D000354	1.50	0.956	0.956
			48.00	49.50	D000355	1.50	0.563	0.563
			49.50	51.00	D000356	1.50	0.798	0.798
			51.00	52.50	D000357	1.50	0.400	0.400
			52.50	54.00	D000358	1.50	0.623	0.623
			54.00	55.50	D000359	1.50	0.904	0.904
			55.50	57.00	D000361	1.50	0.946	0.946
			57.00	58.50	D000362	1.50	1.395	1.395
			58.50	60.00	D000363	1.50	0.359	0.359
			60.00	61.50	D000364	1.50	1.245	1.245
			61.50	63.00	D000365	1.50	2.360	2.360
			63.00	64.50	D000366	1.50	2.320	2.320
			64.50	66.00	D000367	1.50	3.890	3.750
			66.00	67.50	D000369	1.50	1.375	1.375
			67.50	69.00	D000370	1.50	0.352	0.352

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	69.00	70.50	D000371	1.50	0.244		0.244
	70.50	72.00	D000372	1.50	0.897		0.897
	72.00	73.50	D000373	1.50	0.179		0.179
	73.50	75.00	D000374	1.50	1.615		1.615
	75.00	76.50	D000375	1.50	2.500		2.500
	76.50	78.00	D000376	1.50	2.980		2.980
	78.00	79.50	D000377	1.50	2.650		2.650
	79.50	81.00	D000378	1.50	4.720	4.35	4.350
	81.00	82.50	D000379	1.50	4.110	3.81	3.810
	82.50	84.00	D000381	1.50	2.160		2.160
	84.00	85.50	D000382	1.50	1.505		1.505
	85.50	87.00	D000383	1.50	4.150	4.15	4.150
	87.00	88.50	D000384	1.50	2.510		2.510
	88.50	90.00	D000385	1.50	2.750		2.750
	90.00	91.50	D000386	1.50	2.500		2.500
	91.50	93.00	D000387	1.50	2.380		2.380
	93.00	94.50	D000389	1.50	2.460		2.460
	94.50	96.00	D000390	1.50	4.070	3.86	3.860
	96.00	97.50	D000391	1.50	6.300	5.61	5.610
	97.50	99.00	D000392	1.50	4.660	4.62	4.620
	99.00	100.50	D000393	1.50	2.180		2.180
	100.50	102.00	D000394	1.50	3.770	3.56	3.560
	102.00	103.70	D000395	1.70	1.755		1.755
	103.70	105.00	D000396	1.30	>10.0	119.50	119.500
	105.00	106.50	D000397	1.50	4.180	3.84	3.840
	106.50	108.00	D000398	1.50	7.830	5.85	5.850
	108.00	109.50	D000399	1.50	1.985		1.985
	109.50	111.00	D000401	1.50	5.050	4.00	4.000
	111.00	112.50	D000402	1.50	4.880	4.57	4.570
	112.50	114.00	D000403	1.50	3.740	3.73	3.730
	114.00	115.50	D000404	1.50	3.990	3.85	3.850
	115.50	117.00	D000405	1.50	4.260	4.11	4.110
	117.00	118.50	D000406	1.50	3.640	3.35	3.350

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	118.50	120.00	D000407	1.50	1.955		1.955
	120.00	121.50	D000409	1.50	1.560		1.560
	121.50	123.00	D000410	1.50	4.340	4.55	4.550
	123.00	124.50	D000411	1.50	7.260	7.35	7.350
	124.50	126.00	D000412	1.50	5.080	4.67	4.670
	126.00	127.50	D000413	1.50	>10.0	10.75	10.750
	127.50	129.00	D000414	1.50	3.950	4.04	4.040
	129.00	130.50	D000415	1.50	3.930	3.78	3.780
	130.50	132.00	D000416	1.50	4.310	4.44	4.440
	132.00	133.50	D000417	1.50	2.990		2.990
	133.50	135.00	D000418	1.50	3.320	3.35	3.350
	135.00	136.50	D000419	1.50	1.115		1.115
	136.50	138.00	D000421	1.50	0.055		0.055
	138.00	139.50	D000422	1.50	0.017		0.017
	139.50	141.00	D000423	1.50	0.034		0.034
	141.00	142.50	D000424	1.50	1.495		1.495
	142.50	144.00	D000425	1.50	0.211		0.211
	144.00	145.00	D000426	1.00	0.833		0.833
	145.00	146.00	D000427	1.00	0.029		0.029
	146.00	147.00	D000429	1.00	0.023		0.023
	147.00	148.00	D000430	1.00	<0.005		0.001
	148.00	149.40	D000431	1.40	0.061		0.061
	149.40	151.00	D000432	1.60	0.017		0.017
	151.00	152.50	D000433	1.50	0.026		0.026
	152.50	154.00	D000434	1.50	0.016		0.016
	154.00	155.50	D000435	1.50	0.033		0.033
	155.50	157.00	D000436	1.50	0.072		0.072
	157.00	158.50	D000437	1.50	0.648		0.648
	158.50	160.00	D000438	1.50	1.375		1.375
	160.00	161.50	D000439	1.50	0.082		0.082
	161.50	163.00	D000441	1.50	0.088		0.088
	163.00	164.50	D000442	1.50	0.018		0.018
	164.50	166.00	D000443	1.50	0.122		0.122

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			166.00	167.50	D000444	1.50		0.146
			167.50	169.00	D000445	1.50		0.007
			169.00	170.50	D000446	1.50		0.007
			170.50	172.00	D000447	1.50		0.070
			172.00	173.50	D000449	1.50		0.036
			173.50	175.00	D000450	1.50		<0.005
			175.00	176.50	D000451	1.50		0.010
			176.50	178.00	D000452	1.50		0.276
			178.00	179.50	D000453	1.50		<0.005
			179.50	181.00	D000454	1.50		<0.005
			181.00	182.50	D000455	1.50		0.013
			182.50	184.00	D000456	1.50		<0.005
			184.00	185.50	D000457	1.50		<0.005
			185.50	187.00	D000458	1.50		<0.005
			187.00	188.50	D000459	1.50		<0.005
			188.50	190.20	D000461	1.70		<0.005
			190.20	191.30	D000462	1.10		0.123
191.30	192.70	UM <b>Ultramafique</b> Ultramafique	191.30	192.70	D000463	1.40		<0.005
192.70	194.00	SY <b>Syénite</b> Syénite	192.70	194.00	D000464	1.30		<0.005
194.00	247.00	BA <b>Basalte</b> Basalte	194.00	195.50	D000465	1.50		<0.005
			195.50	197.00	D000466	1.50		<0.005
			197.00	198.50	D000467	1.50		<0.005
			198.50	200.00	D000469	1.50		<0.005
			200.00	201.50	D000470	1.50		<0.005
			201.50	203.00	D000471	1.50		<0.005
			203.00	204.50	D000472	1.50		<0.005
			204.50	206.00	D000473	1.50		<0.005
			206.00	207.50	D000474	1.50		0.007
			207.50	209.00	D000475	1.50		0.196
			209.00	210.50	D000476	1.50		0.682

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			210.50	212.00	D000477	1.50	1.110		1.110
			212.00	213.50	D000478	1.50	0.536		0.536
			213.50	215.00	D000479	1.50	0.273		0.273
			215.00	216.50	D000481	1.50	0.021		0.021
			216.50	218.00	D000482	1.50	2.270		2.270
			218.00	219.50	D000483	1.50	0.547		0.547
			219.50	221.00	D000484	1.50	0.054		0.054
			221.00	222.50	D000485	1.50	0.143		0.143
			222.50	224.00	D000486	1.50	1.765		1.765
			224.00	225.50	D000487	1.50	1.510		1.510
			225.50	227.00	D000489	1.50	0.734		0.734
			227.00	228.50	D000490	1.50	0.269		0.269
			228.50	230.00	D000491	1.50	0.416		0.416
			230.00	231.50	D000492	1.50	1.100		1.100
			231.50	233.00	D000493	1.50	0.048		0.048
			233.00	234.50	D000494	1.50	<0.005		0.001
			234.50	236.00	D000495	1.50	0.139		0.139
			236.00	237.50	D000496	1.50	0.539		0.539
			237.50	239.00	D000497	1.50	1.320		1.320
			239.00	240.50	D000498	1.50	0.009		0.009
			240.50	242.00	D000499	1.50	0.005		0.005
			242.00	243.50	D000501	1.50	<0.005		0.001
			243.50	245.00	D000502	1.50	0.298		0.298
			245.00	246.00	D000503	1.00	0.884		0.884
			246.00	247.00	D000504	1.00	0.491		0.491
247.00	247.60	LOST LOST Carottes perdues							
247.60	395.00	BA Basalte Basalte	247.60	249.00	D000505	1.40	0.039		0.039
			249.00	250.50	D000506	1.50	<0.005		0.001
			250.50	252.00	D000507	1.50	<0.005		0.001
			252.00	253.50	D000509	1.50	<0.005		0.001
			253.50	255.00	D000510	1.50	<0.005		0.001
			255.00	256.50	D000511	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	256.50	258.00	D000512	1.50	<0.005		0.001
	258.00	259.50	D000513	1.50	<0.005		0.001
	259.50	261.00	D000514	1.50	<0.005		0.001
	261.00	262.50	D000515	1.50	<0.005		0.001
	262.50	264.00	D000516	1.50	<0.005		0.001
	264.00	265.50	D000517	1.50	<0.005		0.001
	265.50	267.00	D000518	1.50	<0.005		0.001
	267.00	268.50	D000519	1.50	<0.005		0.001
	268.50	270.00	D000521	1.50	<0.005		0.001
	270.00	271.50	D000522	1.50	<0.005		0.001
	271.50	273.00	D000523	1.50	<0.005		0.001
	273.00	274.50	D000524	1.50	<0.005		0.001
	274.50	276.00	D000525	1.50	<0.005		0.001
	276.00	277.50	D000526	1.50	<0.005		0.001
	277.50	279.00	D000527	1.50	<0.005		0.001
	279.00	280.50	D000529	1.50	0.005		0.005
	280.50	282.00	D000530	1.50	<0.005		0.001
	282.00	283.50	D000531	1.50	<0.005		0.001
	283.50	285.00	D000532	1.50	<0.005		0.001
	285.00	286.50	D000533	1.50	<0.005		0.001
	286.50	288.00	D000534	1.50	<0.005		0.001
	288.00	289.50	D000535	1.50	<0.005		0.001
	289.50	291.00	D000536	1.50	<0.005		0.001
	291.00	292.50	D000537	1.50	<0.005		0.001
	292.50	294.00	D000538	1.50	<0.005		0.001
	294.00	295.50	D000539	1.50	<0.005		0.001
	295.50	297.00	D000541	1.50	<0.005		0.001
	297.00	298.50	D000542	1.50	<0.005		0.001
	298.50	300.00	D000543	1.50	<0.005		0.001
	300.00	301.50	D000544	1.50	<0.005		0.001
	301.50	303.00	D000545	1.50	<0.005		0.001
	303.00	304.50	D000546	1.50	<0.005		0.001
	304.50	306.00	D000547	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	306.00	307.50	D000549	1.50	<0.005		0.001
	307.50	309.00	D000550	1.50	<0.005		0.001
	309.00	310.50	D000551	1.50	<0.005		0.001
	310.50	312.00	D000552	1.50	<0.005		0.001
	312.00	313.50	D000553	1.50	<0.005		0.001
	313.50	315.00	D000554	1.50	<0.005		0.001
	315.00	316.50	D000555	1.50	<0.005		0.001
	316.50	318.00	D000556	1.50	<0.005		0.001
	318.00	319.50	D000557	1.50	<0.005		0.001
	319.50	321.00	D000558	1.50	<0.005		0.001
	321.00	322.50	D000559	1.50	<0.005		0.001
	322.50	324.00	D000561	1.50	<0.005		0.001
	324.00	325.50	D000562	1.50	<0.005		0.001
	325.50	327.00	D000563	1.50	<0.005		0.001
	327.00	328.50	D000564	1.50	<0.005		0.001
	328.50	330.00	D000565	1.50	<0.005		0.001
	330.00	331.50	D000566	1.50	<0.005		0.001
	331.50	333.00	D000567	1.50	<0.005		0.001
	333.00	334.50	D000569	1.50	<0.005		0.001
	334.50	336.00	D000570	1.50	<0.005		0.001
	336.00	337.50	D000571	1.50	<0.005		0.001
	337.50	339.00	D000572	1.50	<0.005		0.001
	339.00	340.50	D000573	1.50	<0.005		0.001
	340.50	342.00	D000574	1.50	<0.005		0.001
	342.00	343.50	D000575	1.50	<0.005		0.001
	343.50	345.00	D000576	1.50	<0.005		0.001
	345.00	346.50	D000577	1.50	<0.005		0.001
	346.50	348.00	D000578	1.50	<0.005		0.001
	348.00	349.50	D000579	1.50	<0.005		0.001
	349.50	351.00	D000581	1.50	<0.005		0.001
	351.00	352.50	D000582	1.50	<0.005		0.001
	352.50	354.00	D000583	1.50	<0.005		0.001
	354.00	355.50	D000584	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	355.50	357.00	D000585	1.50	<0.005		0.001
	357.00	358.50	D000586	1.50	<0.005		0.001
	358.50	360.00	D000587	1.50	<0.005		0.001
	360.00	361.50	D000589	1.50	<0.005		0.001
	361.50	363.00	D000590	1.50	<0.005		0.001
	363.00	364.50	D000591	1.50	<0.005		0.001
	364.50	366.00	D000592	1.50	<0.005		0.001
	366.00	367.50	D000593	1.50	<0.005		0.001
	367.50	369.00	D000594	1.50	<0.005		0.001
	369.00	370.50	D000595	1.50	<0.005		0.001
	370.50	372.00	D000596	1.50	<0.005		0.001
	372.00	373.50	D000597	1.50	<0.005		0.001
	373.50	375.00	D000598	1.50	<0.005		0.001
	375.00	376.50	D000599	1.50	0.006		0.006
	376.50	378.00	D000601	1.50	<0.005		0.001
	378.00	379.50	D000602	1.50	<0.005		0.001
	379.50	381.00	D000603	1.50	<0.005		0.001
	381.00	382.50	D000604	1.50	<0.005		0.001
	382.50	384.00	D000605	1.50	<0.005		0.001
	384.00	385.50	D000606	1.50	<0.005		0.001
	385.50	387.00	D000607	1.50	<0.005		0.001
	387.00	388.50	D000609	1.50	<0.005		0.001
	388.50	390.00	D000610	1.50	<0.005		0.001
	390.00	391.50	D000611	1.50	<0.005		0.001
	391.50	393.00	D000612	1.50	<0.005		0.001
	393.00	394.00	D000613	1.00	<0.005		0.001
	394.00	395.00	D000614	1.00	<0.005		0.001
395.00	Fin du sondage Nombre d'échantillons : 248 Nombre d'échantillons QAQC : 27 Longueur totale échantillonnée : 367.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
40.00	40.00	D000349	D000348	0.00	0.631	0.631
55.50	55.50	D000360	A3	0.00	0.611	0.611
66.00	66.00	D000368	D000367	0.00	3.570	3.400
82.50	82.50	D000380	B4	0.00	2.650	2.650
93.00	93.00	D000388	D000387	0.00	2.040	2.040
109.50	109.50	D000400	M1	0.00	0.006	0.006
120.00	120.00	D000408	D000407	0.00	1.985	1.985
136.50	136.50	D000420	C3	0.00	1.405	1.405
146.00	146.00	D000428	D000427	0.00	0.030	0.030
161.50	161.50	D000440	D2	0.00	0.911	0.911
172.00	172.00	D000448	D000447	0.00	0.035	0.035
188.50	188.50	D000460	M1	0.00	<0.005	0.001
198.50	198.50	D000468	D000467	0.00	<0.005	0.001
215.00	215.00	D000480	G2	0.00	4.050	4.100
225.50	225.50	D000488	D000487	0.00	1.825	1.825
242.00	242.00	D000500	H	0.00	0.977	0.977
252.00	252.00	D000508	D000507	0.00	<0.005	0.001
268.50	268.50	D000520	M1	0.00	<0.005	0.001
279.00	279.00	D000528	D000527	0.00	<0.005	0.001
295.50	295.50	D000540	A3	0.00	0.550	0.550
306.00	306.00	D000548	D000547	0.00	<0.005	0.001
322.50	322.50	D000560	B4	0.00	2.570	2.570
333.00	333.00	D000568	D000567	0.00	<0.005	0.001
349.50	349.50	D000580	M1	0.00	<0.005	0.001
360.00	360.00	D000588	D000587	0.00	<0.005	0.001
376.50	376.50	D000600	C3	0.00	1.355	1.355
387.00	387.00	D000608	D000607	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-118**

Titre minier :

Section :                      630100

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles Kamta

Lot :

Du :                              2010-02-28

Date de description :

Au :                              2010-03-05

Collet

UTM

Azimut :                      180.00°

Plongée :                      -60.00°

Longueur :                      251.10 m

Est                              630 100.2

Nord                              5 374 399.9

Élévation                      283.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	307.20°	-60.10°	Oui
Reflex	5.00	306.30°	-60.70°	Oui
Reflex	8.00	307.00°	-60.20°	Oui
Reflex	11.00	344.90°	-59.30°	Oui
Reflex	14.00	52.30°	-58.90°	Oui
Reflex	17.00	29.60°	-59.50°	Oui
Reflex	20.00	181.70°	-59.50°	Non
Reflex	23.00	181.10°	-59.50°	Non
Reflex	26.00	179.60°	-59.40°	Non
Reflex	29.00	180.30°	-59.40°	Non
Reflex	32.00	179.70°	-59.50°	Non
Reflex	35.00	180.40°	-59.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	181.60°	-59.50°	Non
Reflex	41.00	183.40°	-59.50°	Oui
Reflex	44.00	181.40°	-59.20°	Non
Reflex	47.00	182.10°	-59.50°	Non
Reflex	50.00	182.20°	-59.50°	Non
Reflex	53.00	182.00°	-59.50°	Non
Reflex	56.00	181.80°	-59.50°	Non
Reflex	59.00	181.30°	-59.40°	Non
Reflex	62.00	181.20°	-59.40°	Non
Reflex	65.00	181.40°	-59.40°	Non
Reflex	68.00	181.50°	-59.40°	Non
Reflex	71.00	180.20°	-59.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	180.30°	-59.40°	Non	Reflex	173.00	182.70°	-59.00°	Non
Reflex	77.00	180.60°	-59.30°	Non	Reflex	176.00	181.70°	-58.90°	Non
Reflex	80.00	181.10°	-59.30°	Non	Reflex	179.00	181.30°	-58.90°	Non
Reflex	83.00	181.10°	-59.30°	Non	Reflex	182.00	182.10°	-58.90°	Non
Reflex	86.00	181.20°	-59.30°	Non	Reflex	185.00	182.50°	-59.00°	Non
Reflex	89.00	181.20°	-59.30°	Non	Reflex	188.00	180.50°	-58.90°	Non
Reflex	92.00	180.20°	-59.40°	Non	Reflex	191.00	185.60°	-58.90°	Oui
Reflex	95.00	181.50°	-59.40°	Non	Reflex	194.00	182.60°	-58.90°	Non
Reflex	98.00	181.80°	-59.40°	Non	Reflex	197.00	182.10°	-58.90°	Non
Reflex	101.00	181.10°	-59.40°	Non	Reflex	200.00	183.20°	-58.90°	Non
Reflex	104.00	179.80°	-59.40°	Oui	Reflex	203.00	182.50°	-58.80°	Non
Reflex	107.00	180.50°	-59.30°	Non	Reflex	206.00	182.00°	-58.90°	Non
Reflex	110.00	180.20°	-59.30°	Non	Reflex	209.00	181.20°	-58.80°	Non
Reflex	113.00	183.60°	-59.40°	Oui	Reflex	212.00	182.10°	-58.80°	Non
Reflex	116.00	180.70°	-59.40°	Non	Reflex	215.00	182.30°	-58.80°	Non
Reflex	119.00	180.50°	-59.40°	Non	Reflex	218.00	183.10°	-58.80°	Non
Reflex	122.00	181.90°	-59.40°	Non	Reflex	221.00	183.40°	-58.80°	Non
Reflex	125.00	180.00°	-59.40°	Non	Reflex	224.00	183.70°	-58.80°	Non
Reflex	128.00	183.30°	-59.40°	Oui	Reflex	227.00	183.90°	-58.80°	Non
Reflex	131.00	181.70°	-59.40°	Non	Reflex	230.00	183.60°	-58.80°	Non
Reflex	134.00	180.60°	-59.40°	Non	Reflex	233.00	184.40°	-58.80°	Oui
Reflex	137.00	182.60°	-59.30°	Non	Reflex	236.00	183.60°	-58.70°	Non
Reflex	140.00	182.60°	-59.40°	Non	Reflex	239.00	183.50°	-58.80°	Non
Reflex	143.00	181.70°	-59.20°	Non	Reflex	242.00	183.50°	-58.90°	Non
Reflex	146.00	182.10°	-59.20°	Non	Reflex	245.00	183.80°	-58.70°	Non
Reflex	149.00	184.00°	-59.20°	Oui	Reflex	248.00	184.10°	-58.70°	Non
Reflex	152.00	182.20°	-59.10°	Non	Reflex	251.00	184.00°	-58.70°	Non
Reflex	155.00	181.50°	-59.10°	Non					
Reflex	158.00	180.90°	-59.10°	Non					
Reflex	161.00	181.30°	-59.00°	Non					
Reflex	164.00	182.30°	-58.90°	Non					
Reflex	167.00	181.90°	-58.90°	Non					
Reflex	170.00	182.00°	-58.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	13.40	MT <b>Mort-terrain</b> MT						
13.40	84.30	SY <b>Syénite</b> Syénite porphyrique	13.40	15.00	566139	1.60	<0.005	0.001
			15.00	16.50	566140	1.50	0.022	0.022
			16.50	18.00	566141	1.50	<0.005	0.001
			18.00	19.50	566142	1.50	0.038	0.038
			19.50	21.00	566143	1.50	<0.005	0.001
			21.00	22.50	566144	1.50	0.025	0.025
			22.50	24.00	566145	1.50	0.017	0.017
			24.00	25.50	566146	1.50	<0.005	0.001
			25.50	27.00	566147	1.50	0.015	0.015
			27.00	28.50	566149	1.50	0.109	0.109
			28.50	30.00	566150	1.50	0.036	0.036
			30.00	31.50	566151	1.50	0.351	0.351
			31.50	33.00	566152	1.50	0.121	0.121
			33.00	34.50	566153	1.50	0.052	0.052
			34.50	36.00	566154	1.50	0.005	0.005
			36.00	37.50	566155	1.50	<0.005	0.001
			37.50	39.00	566156	1.50	0.007	0.007
			39.00	40.50	566157	1.50	<0.005	0.001
			40.50	42.00	566158	1.50	<0.005	0.001
			42.00	43.50	566160	1.50	<0.005	0.001
			43.50	45.00	566161	1.50	<0.005	0.001
			45.00	46.50	566162	1.50	<0.005	0.001
			46.50	48.00	566163	1.50	0.007	0.007
			48.00	49.50	566164	1.50	0.008	0.008
			49.50	51.00	566165	1.50	<0.005	0.001
			51.00	52.50	566166	1.50	<0.005	0.001
			52.50	54.00	566167	1.50	<0.005	0.001
			54.00	55.50	566169	1.50	<0.005	0.001
			55.50	57.00	566170	1.50	<0.005	0.001
			57.00	58.50	566171	1.50	0.007	0.007
			58.50	60.00	566172	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			60.00	61.50	566173	1.50	<0.005		0.001
			61.50	63.00	566174	1.50	0.008		0.008
			63.00	64.50	566175	1.50	0.010		0.010
			64.50	66.00	566176	1.50	0.005		0.005
			66.00	67.50	566177	1.50	0.011		0.011
			67.50	69.00	566178	1.50	0.019		0.019
			69.00	70.50	566180	1.50	0.009		0.009
			70.50	72.00	566181	1.50	0.028		0.028
			72.00	73.50	566182	1.50	0.036		0.036
			73.50	75.00	566183	1.50	<0.005		0.001
			75.00	76.50	566184	1.50	0.005		0.005
			76.50	78.00	566185	1.50	<0.005		0.001
			78.00	79.50	566186	1.50	<0.005		0.001
			79.50	81.00	566187	1.50	<0.005		0.001
			81.00	82.30	566189	1.30	<0.005		0.001
			82.30	83.30	566190	1.00	<0.005		0.001
			83.30	84.30	566191	1.00	<0.005		0.001
84.30	86.00	LOST <b>LOST</b> Carottes perdues							
86.00	138.10	SY <b>Syénite</b> Syénite porphirique	86.00	87.50	566192	1.50	<0.005		0.001
			87.50	89.00	566193	1.50	0.031		0.031
			89.00	90.50	566194	1.50	0.006		0.006
			90.50	92.00	566195	1.50	0.013		0.013
			92.00	93.50	566196	1.50	0.053		0.053
			93.50	95.00	566197	1.50	<0.005		0.001
			95.00	96.50	566198	1.50	0.013		0.013
			96.50	98.00	566200	1.50	0.007		0.007
			98.00	99.50	566201	1.50	0.026		0.026
			99.50	101.00	566202	1.50	0.010		0.010
			101.00	102.50	566203	1.50	<0.005		0.001
			102.50	104.00	566204	1.50	0.009		0.009
			104.00	105.50	566205	1.50	0.005		0.005
			105.50	107.00	566206	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			107.00	108.50	566207	1.50		0.008
			108.50	110.00	566209	1.50		<0.005
			110.00	111.50	566210	1.50		0.006
			111.50	113.00	566211	1.50		0.006
			113.00	114.50	566212	1.50		0.013
			114.50	116.00	566213	1.50		0.006
			116.00	117.50	566214	1.50		0.005
			117.50	119.00	566215	1.50		<0.005
			119.00	120.50	566216	1.50		<0.005
			120.50	122.00	566217	1.50		<0.005
			122.00	123.50	566218	1.50		0.009
			123.50	125.00	566220	1.50		0.008
			125.00	126.50	566221	1.50		<0.005
			126.50	128.00	566222	1.50		0.005
			128.00	129.50	566223	1.50		<0.005
			129.50	131.00	566224	1.50		<0.005
			131.00	132.50	566225	1.50		0.011
			132.50	134.00	566226	1.50		<0.005
			134.00	135.50	566227	1.50		<0.005
			135.50	137.00	566229	1.50		<0.005
			137.00	138.10	566230	1.10		<0.005
138.10	140.00	BA	138.10	139.10	566231	1.00		<0.005
		<b>Basalte</b>						
		Basalte	139.10	140.00	566232	0.90		0.128
140.00	224.50	SY	140.00	141.00	566233	1.00		1.700
		<b>Syénite</b>						
		Syénite porphirique	141.00	142.50	566234	1.50		1.845
			142.50	144.00	566235	1.50		0.669
			144.00	145.50	566236	1.50		0.620
			145.50	147.00	566237	1.50		1.505
			147.00	148.50	566238	1.50		0.263
			148.50	150.00	566240	1.50		0.113
			150.00	151.50	566241	1.50		0.081
			151.50	153.00	566242	1.50		0.264
			153.00	154.50	566243	1.50		0.030



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	154.50	156.00	566244	1.50	0.009		0.009
	156.00	157.50	566245	1.50	0.008		0.008
	157.50	158.80	566246	1.30	0.018		0.018
	158.80	159.90	566247	1.10	0.479		0.479
	159.90	161.50	566249	1.60	0.474		0.474
	161.50	163.00	566250	1.50	5.950		5.950
	163.00	164.50	566251	1.50	4.290		4.290
	164.50	166.00	566252	1.50	1.125		1.125
	166.00	167.50	566253	1.50	0.665		0.665
	167.50	169.00	566254	1.50	1.215		1.215
	169.00	170.50	566255	1.50	1.355		1.355
	170.50	172.00	566256	1.50	0.186		0.186
	172.00	173.50	566257	1.50	0.245		0.245
	173.50	175.00	566258	1.50	0.473		0.473
	175.00	176.50	566260	1.50	1.550		1.550
	176.50	178.00	566261	1.50	1.445		1.445
	178.00	179.50	566262	1.50	0.343		0.343
	179.50	181.00	566263	1.50	0.710		0.710
	181.00	182.50	566264	1.50	1.700		1.700
	182.50	184.00	566265	1.50	0.062		0.062
	184.00	185.50	566266	1.50	0.670		0.670
	185.50	187.00	566267	1.50	0.275		0.275
	187.00	188.50	566269	1.50	0.011		0.011
	188.50	190.00	566270	1.50	<0.005		0.001
	190.00	191.50	566271	1.50	0.005		0.005
	191.50	193.00	566272	1.50	0.007		0.007
	193.00	194.50	566273	1.50	0.023		0.023
	194.50	196.00	566274	1.50	0.008		0.008
	196.00	197.50	566275	1.50	0.029		0.029
	197.50	199.00	566276	1.50	0.343		0.343
	199.00	200.50	566277	1.50	0.084		0.084
	200.50	202.00	566278	1.50	0.030		0.030
	202.00	203.50	566280	1.50	0.366		0.366

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			203.50	205.00	566281	1.50		0.158	0.158
			205.00	206.50	566282	1.50		0.103	0.103
			206.50	208.00	566283	1.50		0.056	0.056
			208.00	209.50	566284	1.50		0.081	0.081
			209.50	210.90	566285	1.40		0.608	0.608
			210.90	212.50	566286	1.60		5.330	5.330
			212.50	214.00	566287	1.50		4.530	4.530
			214.00	215.50	566289	1.50		1.280	1.280
			215.50	217.00	566290	1.50		0.977	0.977
			217.00	218.50	566291	1.50		2.250	2.250
			218.50	220.00	566292	1.50		2.370	2.370
			220.00	221.50	566293	1.50		2.890	2.890
			221.50	223.00	566294	1.50		8.080	8.080
			223.00	224.50	566295	1.50		>10.0	12.250
224.50	235.70	UM	224.50	225.50	566296	1.00		0.524	0.524
		<b>Ultramafique</b>	225.50	226.50	566297	1.00		0.285	0.285
		Ultramafique	226.50	228.00	566298	1.50		0.294	0.294
			228.00	229.50	566300	1.50		1.950	1.950
			229.50	231.00	566301	1.50		0.317	0.317
			231.00	232.50	566302	1.50		0.482	0.482
			232.50	234.00	566303	1.50		0.622	0.622
			234.00	235.70	566304	1.70		0.063	0.063
235.70	236.00	LOST							
		<b>LOST</b>							
		Carottes perdues							
236.00	251.10	UM	236.00	237.50	566305	1.50		6.010	6.010
		<b>Ultramafique</b>	237.50	239.00	566306	1.50		2.810	2.810
		Ultramafique	239.00	240.50	566307	1.50		0.843	0.843
			240.50	242.00	566309	1.50		0.093	0.093
			242.00	243.50	566310	1.50		0.008	0.008
			243.50	245.00	566311	1.50		0.005	0.005
			245.00	246.50	566312	1.50		0.006	0.006
			246.50	248.00	566313	1.50		0.006	0.006
			248.00	249.50	566314	1.50		0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	249.50	251.10	566315	1.60	0.008		0.008
251.10      Fin du sondage Nombre d'échantillons : 160 Nombre d'échantillons QAQC : 17 Longueur totale échantillonnée : 235.70							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
27.00	27.00	566148	566147	0.00	<0.005	0.001
42.00	42.00	566159	A3	0.00	0.567	0.567
54.00	54.00	566168	566167	0.00	<0.005	0.001
69.00	69.00	566179	B4	0.00	2.550	2.550
81.00	81.00	566188	566187	0.00	<0.005	0.001
96.50	96.50	566199	M1	0.00	<0.005	0.001
108.50	108.50	566208	566207	0.00	0.005	0.005
123.50	123.50	566219	C3	0.00	0.965	0.965
135.50	135.50	566228	566227	0.00	<0.005	0.001
148.50	148.50	566239	D2	0.00	0.859	0.859
159.90	159.90	566248	566247	0.00	0.403	0.403
175.00	175.00	566259	M1	0.00	<0.005	0.001
187.00	187.00	566268	566267	0.00	0.291	0.291
202.00	202.00	566279	G2	0.00	3.800	3.800
214.00	214.00	566288	566287	0.00	4.630	4.630
228.00	228.00	566299	H	0.00	0.978	0.978
240.50	240.50	566308	566307	0.00	0.938	0.938

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-119**

Titre minier :

Section :                      631300

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              bradley

Lot :

Décrit par :            Gilles.Kamta

Du :                      2010-02-26

Date de description :    2010-03-05

Au :                      2010-03-02

Collet

UTM

Azimut :                0.00°  
 Plongée :               -60.00°  
 Longueur :            431.00 m

Est	631 300.0
Nord	5 374 400.3
Élévation	296.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	77.60°	-60.20°	Oui
Reflex	5.00	351.90°	-60.20°	Oui
Reflex	8.00	359.80°	-60.20°	Non
Reflex	11.00	359.70°	-60.20°	Non
Reflex	14.00	359.50°	-60.10°	Non
Reflex	17.00	359.50°	-60.00°	Non
Reflex	20.00	359.40°	-60.00°	Non
Reflex	23.00	359.50°	-60.00°	Non
Reflex	26.00	359.70°	-60.00°	Non
Reflex	29.00	359.40°	-59.90°	Non
Reflex	32.00	359.50°	-59.70°	Non
Reflex	35.00	359.30°	-59.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.10°	-59.60°	Non
Reflex	41.00	359.10°	-59.50°	Non
Reflex	44.00	359.00°	-59.40°	Non
Reflex	47.00	358.80°	-59.40°	Non
Reflex	50.00	358.80°	-59.40°	Non
Reflex	53.00	358.60°	-59.40°	Non
Reflex	56.00	358.60°	-59.40°	Non
Reflex	59.00	358.30°	-59.40°	Non
Reflex	62.00	358.10°	-59.30°	Non
Reflex	65.00	357.90°	-59.30°	Non
Reflex	68.00	357.40°	-59.20°	Non
Reflex	71.00	359.00°	-59.10°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.70°	-59.10°	Non
Reflex	77.00	0.80°	-59.00°	Non
Reflex	80.00	359.20°	-59.10°	Non
Reflex	83.00	0.40°	-59.00°	Non
Reflex	86.00	1.00°	-59.00°	Non
Reflex	89.00	0.60°	-59.00°	Non
Reflex	92.00	359.90°	-59.00°	Non
Reflex	95.00	1.30°	-59.00°	Non
Reflex	98.00	359.20°	-59.00°	Non
Reflex	101.00	359.50°	-59.00°	Non
Reflex	104.00	0.00°	-59.00°	Non
Reflex	107.00	359.10°	-58.90°	Non
Reflex	110.00	0.80°	-58.80°	Non
Reflex	113.00	359.50°	-58.80°	Non
Reflex	116.00	1.50°	-58.80°	Non
Reflex	119.00	0.30°	-58.80°	Non
Reflex	122.00	359.90°	-58.80°	Non
Reflex	125.00	359.90°	-58.70°	Non
Reflex	128.00	1.10°	-58.70°	Non
Reflex	131.00	0.20°	-58.60°	Non
Reflex	134.00	358.60°	-58.50°	Non
Reflex	137.00	359.90°	-58.50°	Non
Reflex	140.00	0.20°	-58.40°	Non
Reflex	143.00	359.80°	-58.30°	Non
Reflex	146.00	359.90°	-58.20°	Non
Reflex	149.00	359.70°	-58.20°	Non
Reflex	152.00	2.30°	-58.10°	Oui
Reflex	155.00	0.80°	-58.10°	Non
Reflex	158.00	1.00°	-58.10°	Non
Reflex	161.00	2.30°	-58.10°	Non
Reflex	164.00	2.10°	-58.10°	Non
Reflex	167.00	2.40°	-58.00°	Non
Reflex	170.00	1.80°	-57.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	1.30°	-57.90°	Non
Reflex	176.00	1.00°	-57.90°	Non
Reflex	179.00	0.80°	-57.80°	Non
Reflex	182.00	0.70°	-57.80°	Non
Reflex	185.00	0.80°	-57.80°	Non
Reflex	188.00	359.90°	-57.80°	Non
Reflex	191.00	0.80°	-57.70°	Non
Reflex	194.00	358.80°	-57.70°	Non
Reflex	197.00	1.90°	-57.80°	Non
Reflex	200.00	0.90°	-57.70°	Non
Reflex	203.00	359.80°	-57.80°	Non
Reflex	206.00	357.70°	-57.70°	Oui
Reflex	209.00	0.20°	-57.70°	Non
Reflex	212.00	1.60°	-57.70°	Non
Reflex	215.00	2.00°	-57.70°	Non
Reflex	218.00	1.50°	-57.60°	Non
Reflex	221.00	1.40°	-57.60°	Non
Reflex	224.00	1.30°	-57.60°	Non
Reflex	227.00	1.50°	-57.50°	Non
Reflex	230.00	2.30°	-57.60°	Oui
Reflex	233.00	0.90°	-57.50°	Non
Reflex	236.00	1.40°	-57.60°	Non
Reflex	239.00	1.60°	-57.40°	Non
Reflex	242.00	2.00°	-57.50°	Non
Reflex	245.00	1.70°	-57.40°	Non
Reflex	248.00	2.30°	-57.40°	Non
Reflex	251.00	2.20°	-57.40°	Non
Reflex	254.00	2.10°	-57.40°	Non
Reflex	257.00	2.10°	-57.50°	Non
Reflex	260.00	2.90°	-57.40°	Non
Reflex	263.00	2.60°	-57.40°	Non
Reflex	266.00	2.20°	-57.40°	Non
Reflex	269.00	1.80°	-57.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	3.10°	-57.40°	Non	Reflex	371.00	0.60°	-57.10°	Non
Reflex	275.00	4.00°	-57.40°	Non	Reflex	374.00	1.10°	-57.10°	Non
Reflex	278.00	3.70°	-57.40°	Non	Reflex	377.00	1.30°	-57.10°	Non
Reflex	281.00	3.00°	-57.40°	Non	Reflex	380.00	1.50°	-57.10°	Non
Reflex	284.00	1.20°	-57.50°	Non	Reflex	383.00	1.50°	-57.10°	Non
Reflex	287.00	0.80°	-57.40°	Non	Reflex	386.00	1.50°	-57.00°	Non
Reflex	290.00	359.20°	-57.50°	Non	Reflex	389.00	1.60°	-57.00°	Non
Reflex	293.00	358.90°	-57.40°	Non	Reflex	392.00	1.60°	-57.00°	Non
Reflex	296.00	359.30°	-57.40°	Non	Reflex	395.00	1.70°	-57.00°	Non
Reflex	299.00	0.10°	-57.40°	Non	Reflex	398.00	1.80°	-56.90°	Non
Reflex	302.00	0.50°	-57.40°	Non	Reflex	401.00	1.80°	-56.90°	Non
Reflex	305.00	1.40°	-57.40°	Non	Reflex	404.00	1.80°	-56.80°	Non
Reflex	308.00	356.50°	-57.40°	Oui	Reflex	407.00	1.90°	-56.70°	Non
Reflex	311.00	359.00°	-57.40°	Non	Reflex	410.00	2.00°	-56.80°	Non
Reflex	314.00	359.50°	-57.40°	Non	Reflex	413.00	2.10°	-56.70°	Non
Reflex	317.00	359.60°	-57.40°	Non	Reflex	416.00	2.10°	-56.70°	Non
Reflex	320.00	359.50°	-57.40°	Non	Reflex	419.00	2.10°	-56.80°	Non
Reflex	323.00	1.10°	-57.40°	Non	Reflex	422.00	2.20°	-56.80°	Non
Reflex	326.00	1.20°	-57.30°	Non	Reflex	425.00	2.20°	-56.80°	Non
Reflex	329.00	359.90°	-57.30°	Non	Reflex	428.00	2.30°	-56.70°	Non
Reflex	332.00	359.60°	-57.20°	Non	Reflex	431.00	2.20°	-56.70°	Non
Reflex	335.00	358.70°	-57.20°	Non					
Reflex	338.00	359.40°	-57.20°	Non					
Reflex	341.00	359.70°	-57.10°	Non					
Reflex	344.00	0.70°	-57.10°	Non					
Reflex	347.00	359.50°	-57.10°	Non					
Reflex	350.00	0.80°	-57.10°	Non					
Reflex	353.00	0.30°	-57.10°	Non					
Reflex	356.00	1.50°	-57.10°	Non					
Reflex	359.00	1.50°	-57.10°	Non					
Reflex	362.00	0.70°	-57.10°	Non					
Reflex	365.00	0.50°	-57.10°	Non					
Reflex	368.00	1.60°	-57.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.20	MT <b>Mort-terrain</b> MT						
5.20	157.60	SY <b>Syénite</b> Syénite	5.20	6.60	D000615	1.40	0.009	0.009
			6.60	8.00	D000616	1.40	0.043	0.043
			8.00	9.50	D000617	1.50	0.038	0.038
			9.50	11.00	D000618	1.50	0.018	0.018
			11.00	12.50	D000619	1.50	0.098	0.098
			12.50	14.00	D000620	1.50	0.039	0.039
			14.00	15.50	D000621	1.50	0.033	0.033
			15.50	17.00	D000622	1.50	0.013	0.013
			17.00	18.50	D000623	1.50	0.027	0.027
			18.50	20.00	D000625	1.50	0.009	0.009
			20.00	21.50	D000626	1.50	0.025	0.025
			21.50	23.00	D000627	1.50	0.046	0.046
			23.00	24.50	D000628	1.50	0.283	0.283
			24.50	26.00	D000629	1.50	0.008	0.008
			26.00	27.50	D000630	1.50	0.008	0.008
			27.50	29.00	D000631	1.50	0.072	0.072
			29.00	30.50	D000632	1.50	0.018	0.018
			30.50	32.00	D000633	1.50	0.009	0.009
			32.00	33.50	D000634	1.50	0.031	0.031
			33.50	35.00	D000636	1.50	0.634	0.634
			35.00	36.50	D000637	1.50	0.376	0.376
			36.50	38.00	D000638	1.50	0.053	0.053
			38.00	39.50	D000639	1.50	<0.005	0.001
			39.50	41.00	D000640	1.50	0.049	0.049
			41.00	42.50	D000641	1.50	<0.005	0.001
			42.50	44.00	D000642	1.50	<0.005	0.001
			44.00	45.50	D000643	1.50	<0.005	0.001
			45.50	47.00	D000645	1.50	<0.005	0.001
			47.00	48.50	D000646	1.50	0.037	0.037
			48.50	50.00	D000647	1.50	0.018	0.018
			50.00	51.50	D000648	1.50	0.034	0.034



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	51.50	53.00	D000649	1.50	0.051	3.70	0.051
	53.00	54.50	D000650	1.50	0.019		0.019
	54.50	56.00	D000651	1.50	0.036		0.036
	56.00	57.50	D000652	1.50	0.013		0.013
	57.50	59.00	D000653	1.50	0.081		0.081
	59.00	60.50	D000654	1.50	0.042		0.042
	60.50	61.50	D000656	1.00	0.206		0.206
	61.50	63.00	D000657	1.50	3.740		3.700
	63.00	64.50	D000658	1.50	0.165		0.165
	64.50	66.00	D000659	1.50	0.019		0.019
	66.00	67.10	D000660	1.10	<0.005		0.001
	67.10	68.50	D000661	1.40	<0.005		0.001
	68.50	70.00	D000662	1.50	<0.005		0.001
	70.00	71.50	D000663	1.50	<0.005		0.001
	71.50	73.00	D000665	1.50	0.147		0.147
	73.00	74.50	D000666	1.50	0.155		0.155
	74.50	76.00	D000667	1.50	0.005		0.005
	76.00	77.50	D000668	1.50	<0.005		0.001
	77.50	79.00	D000669	1.50	<0.005		0.001
	79.00	80.50	D000670	1.50	<0.005		0.001
	80.50	82.00	D000671	1.50	<0.005		0.001
	82.00	83.50	D000672	1.50	<0.005		0.001
	83.50	85.00	D000673	1.50	<0.005		0.001
	85.00	86.50	D000674	1.50	<0.005		0.001
	86.50	88.00	D000676	1.50	<0.005		0.001
	88.00	89.50	D000677	1.50	<0.005		0.001
	89.50	91.00	D000678	1.50	0.005		0.005
	91.00	92.50	D000679	1.50	0.013		0.013
	92.50	94.00	D000680	1.50	<0.005	0.001	
	94.00	95.50	D000681	1.50	<0.005	0.001	
	95.50	96.80	D000682	1.30	<0.005	0.001	
	96.80	98.00	D000683	1.20	<0.005	0.001	
	98.00	99.50	D000685	1.50	0.016	0.016	

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	99.50	100.50	D000686	1.00	0.010		0.010
	100.50	102.00	D000687	1.50	0.005		0.005
	102.00	103.50	D000688	1.50	<0.005		0.001
	103.50	105.00	D000689	1.50	<0.005		0.001
	105.00	106.50	D000690	1.50	0.071		0.071
	106.50	108.00	D000691	1.50	0.013		0.013
	108.00	109.50	D000692	1.50	0.048		0.048
	109.50	111.00	D000693	1.50	0.009		0.009
	111.00	112.50	D000694	1.50	0.005		0.005
	112.50	114.00	D000696	1.50	0.005		0.005
	114.00	115.50	D000697	1.50	0.173		0.173
	115.50	117.00	D000698	1.50	0.006		0.006
	117.00	118.50	D000699	1.50	0.071		0.071
	118.50	120.00	D000700	1.50	0.006		0.006
	120.00	121.50	D000701	1.50	0.007		0.007
	121.50	123.00	D000702	1.50	0.054		0.054
	123.00	124.50	D000703	1.50	0.028		0.028
	124.50	126.00	D000705	1.50	0.042		0.042
	126.00	127.50	D000706	1.50	0.052		0.052
	127.50	129.00	D000707	1.50	0.008		0.008
	129.00	130.50	D000708	1.50	0.066		0.066
	130.50	132.00	D000709	1.50	0.005		0.005
	132.00	133.00	D000710	1.00	0.025		0.025
	133.00	134.50	D000711	1.50	0.114		0.114
	134.50	136.00	D000712	1.50	0.019		0.019
	136.00	137.50	D000713	1.50	0.064		0.064
	137.50	139.00	D000714	1.50	0.042		0.042
	139.00	140.50	D000716	1.50	0.135		0.135
	140.50	142.00	D000717	1.50	0.017		0.017
	142.00	143.50	D000718	1.50	1.650		1.650
	143.50	144.60	D000719	1.10	0.056		0.056
	144.60	146.00	D000720	1.40	<0.005		0.001
	146.00	147.50	D000721	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			147.50	149.00	D000722	1.50		0.030	0.030
			149.00	150.50	D000723	1.50		0.051	0.051
			150.50	152.00	D000725	1.50		<0.005	0.001
			152.00	153.50	D000726	1.50		0.785	0.785
			153.50	155.00	D000727	1.50		0.014	0.014
			155.00	156.50	D000728	1.50		<0.005	0.001
			156.50	157.60	D000729	1.10		<0.005	0.001
157.60	158.00	NR Carotte perdue							
		LOST							
158.00	348.70	SY Syénite	158.00	159.50	D000730	1.50		0.138	0.138
			159.50	161.00	D000731	1.50		<0.005	0.001
			161.00	162.50	D000732	1.50		0.099	0.099
			162.50	164.00	D000733	1.50		0.011	0.011
			164.00	165.50	D000734	1.50		0.078	0.078
			165.50	167.00	D000736	1.50		1.240	1.240
			167.00	168.50	D000737	1.50		0.131	0.131
			168.50	169.80	D000738	1.30		0.201	0.201
			169.80	171.00	D000739	1.20		0.012	0.012
			171.00	172.00	D000740	1.00		0.201	0.201
			172.00	173.50	D000741	1.50		0.029	0.029
			173.50	175.00	D000742	1.50		0.022	0.022
			175.00	176.50	D000743	1.50		0.050	0.050
			176.50	177.50	D000745	1.00		0.581	0.581
			177.50	178.50	D000746	1.00		0.009	0.009
			178.50	180.00	D000747	1.50		<0.005	0.001
			180.00	181.50	D000748	1.50		0.187	0.187
			181.50	183.00	D000749	1.50		0.171	0.171
			183.00	184.50	D000750	1.50		0.152	0.152
			184.50	186.00	D000751	1.50		0.634	0.634
			186.00	187.50	D000752	1.50		1.335	1.335
			187.50	189.00	D000753	1.50		0.142	0.142
			189.00	190.50	D000754	1.50		0.005	0.005
			190.50	192.00	D000756	1.50		0.066	0.066

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	192.00	193.50	D000757	1.50	0.221		0.221
	193.50	195.00	D000758	1.50	<0.005		0.001
	195.00	196.50	D000759	1.50	0.041		0.041
	196.50	198.00	D000760	1.50	0.063		0.063
	198.00	199.00	D000761	1.00	0.056		0.056
	199.00	200.50	D000762	1.50	0.005		0.005
	200.50	202.00	D000763	1.50	0.036		0.036
	202.00	203.50	D000765	1.50	0.025		0.025
	203.50	205.00	D000766	1.50	0.041		0.041
	205.00	206.50	D000767	1.50	0.121		0.121
	206.50	208.00	D000768	1.50	<0.005		0.001
	208.00	209.50	D000769	1.50	0.113		0.113
	209.50	211.00	D000770	1.50	0.005		0.005
	211.00	212.50	D000771	1.50	0.006		0.006
	212.50	214.00	D000772	1.50	<0.005		0.001
	214.00	215.50	D000773	1.50	0.008		0.008
	215.50	217.00	D000774	1.50	<0.005		0.001
	217.00	218.50	D000776	1.50	<0.005		0.001
	218.50	220.00	D000777	1.50	0.504		0.504
	220.00	221.50	D000778	1.50	0.022		0.022
	221.50	223.00	D000779	1.50	0.164		0.164
	223.00	224.50	D000780	1.50	0.263		0.263
	224.50	226.00	D000781	1.50	0.006		0.006
	226.00	227.50	D000782	1.50	0.008		0.008
	227.50	229.00	D000783	1.50	<0.005		0.001
	229.00	230.50	D000785	1.50	0.019		0.019
	230.50	232.00	D000786	1.50	0.018		0.018
	232.00	233.50	D000787	1.50	<0.005		0.001
	233.50	235.00	D000788	1.50	0.005		0.005
	235.00	236.50	D000789	1.50	<0.005		0.001
	236.50	238.00	D000790	1.50	<0.005		0.001
	238.00	239.50	D000791	1.50	0.028		0.028
	239.50	241.00	D000792	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	241.00	242.50	D000793	1.50	<0.005		0.001
	242.50	244.00	D000794	1.50	<0.005		0.001
	244.00	245.50	D000796	1.50	0.007		0.007
	245.50	247.00	D000797	1.50	<0.005		0.001
	247.00	248.50	D000798	1.50	<0.005		0.001
	248.50	250.00	D000799	1.50	<0.005		0.001
	250.00	251.50	D000800	1.50	<0.005		0.001
	251.50	253.00	D000801	1.50	<0.005		0.001
	253.00	254.50	D000802	1.50	<0.005		0.001
	254.50	256.00	D000803	1.50	<0.005		0.001
	256.00	257.50	D000805	1.50	<0.005		0.001
	257.50	259.00	D000806	1.50	<0.005		0.001
	259.00	260.50	D000807	1.50	<0.005		0.001
	260.50	262.00	D000808	1.50	<0.005		0.001
	262.00	263.50	D000809	1.50	<0.005		0.001
	263.50	265.00	D000810	1.50	<0.005		0.001
	265.00	266.50	D000811	1.50	<0.005		0.001
	266.50	268.00	D000812	1.50	<0.005		0.001
	268.00	269.50	D000813	1.50	<0.005		0.001
	269.50	271.00	D000814	1.50	<0.005		0.001
	271.00	272.50	D000816	1.50	<0.005		0.001
	272.50	273.60	D000817	1.10	0.006		0.006
	273.60	274.90	D000818	1.30	0.215		0.215
	274.90	276.50	D000819	1.60	0.802		0.802
	276.50	278.00	D000820	1.50	0.293		0.293
	278.00	279.50	D000821	1.50	0.740		0.740
	279.50	281.00	D000822	1.50	0.112		0.112
	281.00	282.40	D000823	1.40	0.005		0.005
	282.40	283.40	D000825	1.00	0.006		0.006
	283.40	285.00	D000826	1.60	0.022		0.022
	285.00	286.30	D000827	1.30	0.024		0.024
	286.30	287.50	D000828	1.20	0.203		0.203
	287.50	289.00	D000829	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	289.00	290.50	D000830	1.50	0.009		0.009
	290.50	292.00	D000831	1.50	0.013		0.013
	292.00	293.50	D000832	1.50	<0.005		0.001
	293.50	295.00	D000833	1.50	0.009		0.009
	295.00	296.50	D000834	1.50	0.014		0.014
	296.50	298.00	D000836	1.50	<0.005		0.001
	298.00	299.50	D000837	1.50	0.018		0.018
	299.50	301.00	D000838	1.50	<0.005		0.001
	301.00	302.50	D000839	1.50	0.007		0.007
	302.50	304.00	D000840	1.50	0.059		0.059
	304.00	305.50	D000841	1.50	0.066		0.066
	305.50	307.00	D000842	1.50	0.205		0.205
	307.00	308.50	D000843	1.50	0.082		0.082
	308.50	310.00	D000845	1.50	0.051		0.051
	310.00	311.50	D000846	1.50	0.158		0.158
	311.50	313.00	D000847	1.50	0.117		0.117
	313.00	314.00	D000848	1.00	0.162		0.162
	314.00	315.50	D000849	1.50	0.325		0.325
	315.50	317.00	D000850	1.50	0.067		0.067
	317.00	318.50	D000851	1.50	0.097		0.097
	318.50	319.50	D000852	1.00	0.086		0.086
	319.50	321.00	D000853	1.50	0.011		0.011
	321.00	322.50	D000854	1.50	0.020		0.020
	322.50	324.00	D000856	1.50	0.041		0.041
	324.00	325.50	D000857	1.50	0.011		0.011
	325.50	327.00	D000858	1.50	0.020		0.020
	327.00	328.50	D000859	1.50	0.021		0.021
	328.50	330.00	D000860	1.50	<0.005		0.001
	330.00	331.50	D000861	1.50	0.054		0.054
	331.50	333.00	D000862	1.50	0.011		0.011
	333.00	334.50	D000863	1.50	0.019		0.019
	334.50	336.00	D000865	1.50	0.083		0.083
	336.00	337.50	D000866	1.50	0.150		0.150

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			337.50	339.00	D000867	1.50		0.026		0.026
			339.00	340.50	D000868	1.50		0.086		0.086
			340.50	342.00	D000869	1.50		0.023		0.023
			342.00	343.00	D000870	1.00		0.055		0.055
			343.00	344.50	D000871	1.50		0.038		0.038
			344.50	346.00	D000872	1.50		0.013		0.013
			346.00	347.50	D000873	1.50		0.038		0.038
			347.50	348.70	D000874	1.20		0.019		0.019
348.70	349.00	NR Carotte perdue LOST								
349.00	377.10	SY Syénite Syénite	349.00	350.50	D000876	1.50		<0.005		0.001
			350.50	352.00	D000877	1.50		<0.005		0.001
			352.00	353.50	D000878	1.50		0.007		0.007
			353.50	354.50	D000879	1.00		0.041		0.041
			354.50	356.00	D000880	1.50		<0.005		0.001
			356.00	357.50	D000881	1.50		0.010		0.010
			357.50	359.00	D000882	1.50		0.040		0.040
			359.00	360.50	D000883	1.50		0.032		0.032
			360.50	362.00	D000885	1.50		0.038		0.038
			362.00	363.50	D000886	1.50		0.017		0.017
			363.50	365.00	D000887	1.50		0.135		0.135
			365.00	366.50	D000888	1.50		1.025		1.025
			366.50	368.00	D000889	1.50		1.100		1.100
			368.00	369.50	D000890	1.50		0.428		0.428
			369.50	371.00	D000891	1.50		1.740		1.740
			371.00	372.60	D000892	1.60		4.910	5.35	5.350
			372.60	374.00	D000893	1.40		>10.0	22.50	22.500
			374.00	375.50	D000894	1.50		2.560		2.560
			375.50	377.10	D000896	1.60		2.500		2.500
377.10	431.00	AN Andésite Andésite	377.10	378.50	D000897	1.40		0.499		0.499
			378.50	380.00	D000898	1.50		0.014		0.014
			380.00	381.50	D000899	1.50		<0.005		0.001
			381.50	383.00	D000900	1.50		0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	383.00	384.50	D000901	1.50	0.007		0.007
	384.50	386.00	D000902	1.50	<0.005		0.001
	386.00	387.50	D000903	1.50	<0.005		0.001
	387.50	389.00	D000905	1.50	<0.005		0.001
	389.00	390.50	D000906	1.50	<0.005		0.001
	390.50	392.00	D000907	1.50	<0.005		0.001
	392.00	393.50	D000908	1.50	<0.005		0.001
	393.50	395.00	D000909	1.50	<0.005		0.001
	395.00	396.50	D000910	1.50	<0.005		0.001
	396.50	398.00	D000911	1.50	<0.005		0.001
	398.00	399.50	D000912	1.50	<0.005		0.001
	399.50	401.00	D000913	1.50	<0.005		0.001
	401.00	402.50	D000914	1.50	<0.005		0.001
	402.50	404.00	D000916	1.50	<0.005		0.001
	404.00	405.50	D000917	1.50	<0.005		0.001
	405.50	407.00	D000918	1.50	<0.005		0.001
	407.00	408.50	D000919	1.50	<0.005		0.001
	408.50	410.00	D000920	1.50	<0.005		0.001
	410.00	411.50	D000921	1.50	<0.005		0.001
	411.50	413.00	D000922	1.50	<0.005		0.001
	413.00	414.50	D000923	1.50	<0.005		0.001
	414.50	416.00	D000925	1.50	<0.005		0.001
	416.00	417.50	D000926	1.50	<0.005		0.001
	417.50	419.00	D000927	1.50	<0.005		0.001
	419.00	420.50	D000928	1.50	<0.005		0.001
	420.50	422.00	D000929	1.50	<0.005		0.001
	422.00	423.50	D000930	1.50	<0.005		0.001
	423.50	425.00	D000931	1.50	<0.005		0.001
	425.00	426.50	D000932	1.50	<0.005		0.001
	426.50	428.00	D000934	1.50	<0.005		0.001
	428.00	429.50	D000935	1.50	<0.005		0.001
	429.50	431.00	D000936	1.50	<0.005		0.001



431.00

Fin du sondage

Nombre d'échantillons : 290

Nombre d'échantillons QAQC : 32

Longueur totale échantillonnée : 425.10

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
18.50	18.50	D000624	D000623	0.00	0.028	0.028
33.50	33.50	D000635	A3	0.00	0.586	0.586
45.50	45.50	D000644	D000643	0.00	<0.005	0.001
60.50	61.50	D000655	M1	1.00	<0.005	0.001
71.50	71.50	D000664	D000663	0.00	<0.005	0.001
86.50	86.50	D000675	B4	0.00	2.660	2.660
98.00	98.00	D000684	D000683	0.00	<0.005	0.001
112.50	112.50	D000695	M1	0.00	<0.005	0.001
124.50	124.50	D000704	D000703	0.00	0.027	0.027
139.00	139.00	D000715	C3	0.00	1.325	1.325
150.50	150.50	D000724	D000723	0.00	0.070	0.070
165.50	165.50	D000735	M1	0.00	<0.005	0.001
176.50	176.50	D000744	D000743	0.00	0.050	0.050
190.50	190.50	D000755	D2	0.00	0.755	0.755
202.00	202.00	D000764	D000763	0.00	0.050	0.050
217.00	217.00	D000775	M1	0.00	<0.005	0.001
229.00	229.00	D000784	D000783	0.00	<0.005	0.001
244.00	244.00	D000795	G2	0.00	3.960	4.240
256.00	256.00	D000804	D000803	0.00	<0.005	0.001
271.00	271.00	D000815	H	0.00	0.988	0.988
282.40	282.40	D000824	D000823	0.00	<0.005	0.001
296.50	296.50	D000835	M1	0.00	<0.005	0.001
308.50	308.50	D000844	D000843	0.00	0.082	0.082
322.50	322.50	D000855	A3	0.00	0.612	0.612
334.50	334.50	D000864	D000863	0.00	0.027	0.027
349.00	348.70	D000875	M1	-0.30	<0.005	0.001
360.50	360.50	D000884	D000883	0.00	0.035	0.035
375.50	375.50	D000895	B4	0.00	2.530	2.530
387.50	387.50	D000904	D000903	0.00	<0.005	0.001
402.50	402.50	D000915	M1	0.00	<0.005	0.001
414.50	414.50	D000924	D000923	0.00	<0.005	0.001
426.50	426.50	D000933	C3	0.00	1.315	1.315

## Corporation Minière Osisko Div. Exploration

**Sondage :**        **BD10-122**

Titre minier :

Section :                    631300

Canton :

Niveau :

Rang :

Place de travail :

Foré par :                Bradley

Lot :

Décrit par :             David.Ruahra

Du :                        2010-03-02

Date de description :

Au :                        2010-03-07

Collet

UTM

Azimut :                 0.00°  
 Plongée :                -60.00°  
 Longueur :              470.70 m

Est	631 300.1
Nord	5 374 350.1
Élévation	299.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	8.40°	-59.50°	Oui
Reflex	11.00	356.10°	-59.60°	Oui
Reflex	14.00	355.40°	-59.70°	Oui
Reflex	17.00	2.70°	-60.20°	Non
Reflex	20.00	1.80°	-59.20°	Non
Reflex	23.00	1.90°	-59.40°	Non
Reflex	26.00	1.30°	-59.40°	Non
Reflex	29.00	1.30°	-59.20°	Non
Reflex	32.00	1.10°	-59.30°	Non
Reflex	35.00	1.40°	-59.30°	Non
Reflex	38.00	1.30°	-59.10°	Non
Reflex	41.00	1.20°	-59.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	1.20°	-59.20°	Non
Reflex	47.00	1.30°	-59.20°	Non
Reflex	50.00	1.40°	-59.00°	Non
Reflex	53.00	1.10°	-59.00°	Non
Reflex	56.00	357.50°	-52.00°	Oui
Reflex	59.00	1.10°	-59.10°	Non
Reflex	62.00	1.20°	-59.20°	Non
Reflex	65.00	1.10°	-59.10°	Non
Reflex	68.00	1.00°	-59.10°	Non
Reflex	71.00	0.90°	-58.90°	Non
Reflex	74.00	0.70°	-58.80°	Non
Reflex	77.00	1.60°	-58.60°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	4.20°	-58.60°	Oui	Reflex	179.00	3.40°	-57.80°	Non
Reflex	83.00	1.40°	-58.60°	Non	Reflex	182.00	3.40°	-57.80°	Non
Reflex	86.00	0.80°	-58.60°	Non	Reflex	185.00	2.90°	-57.70°	Non
Reflex	89.00	0.90°	-58.60°	Non	Reflex	188.00	2.10°	-57.70°	Non
Reflex	92.00	0.30°	-58.50°	Non	Reflex	191.00	3.60°	-57.70°	Non
Reflex	95.00	1.60°	-58.60°	Non	Reflex	194.00	2.60°	-57.90°	Non
Reflex	98.00	0.90°	-58.70°	Non	Reflex	197.00	2.00°	-57.60°	Non
Reflex	101.00	1.70°	-58.50°	Non	Reflex	200.00	1.20°	-57.60°	Non
Reflex	104.00	2.50°	-58.60°	Non	Reflex	203.00	1.90°	-57.60°	Non
Reflex	107.00	359.80°	-58.50°	Non	Reflex	206.00	2.60°	-57.60°	Non
Reflex	110.00	1.30°	-58.50°	Non	Reflex	209.00	2.90°	-57.60°	Non
Reflex	113.00	3.40°	-58.40°	Oui	Reflex	212.00	2.00°	-57.60°	Non
Reflex	116.00	2.00°	-58.40°	Non	Reflex	215.00	2.10°	-57.50°	Non
Reflex	119.00	0.70°	-58.40°	Non	Reflex	218.00	3.10°	-57.60°	Non
Reflex	122.00	0.70°	-58.40°	Non	Reflex	221.00	2.60°	-57.50°	Non
Reflex	125.00	0.90°	-58.40°	Non	Reflex	224.00	3.50°	-57.50°	Non
Reflex	128.00	1.00°	-58.40°	Non	Reflex	227.00	3.40°	-57.50°	Non
Reflex	131.00	0.50°	-58.00°	Non	Reflex	230.00	2.10°	-57.50°	Non
Reflex	134.00	1.10°	-58.30°	Non	Reflex	233.00	3.20°	-57.50°	Non
Reflex	137.00	1.40°	-58.30°	Non	Reflex	236.00	3.60°	-57.50°	Non
Reflex	140.00	1.10°	-58.20°	Non	Reflex	239.00	2.90°	-57.40°	Non
Reflex	143.00	2.20°	-58.20°	Non	Reflex	242.00	2.80°	-57.40°	Non
Reflex	146.00	1.80°	-58.20°	Non	Reflex	245.00	3.40°	-57.40°	Non
Reflex	149.00	3.50°	-58.20°	Non	Reflex	248.00	2.20°	-57.30°	Non
Reflex	152.00	3.40°	-58.60°	Non	Reflex	251.00	3.70°	-57.40°	Non
Reflex	155.00	3.60°	-58.00°	Non	Reflex	254.00	3.00°	-57.40°	Non
Reflex	158.00	358.00°	-58.00°	Oui	Reflex	257.00	4.00°	-57.30°	Oui
Reflex	161.00	1.50°	-58.00°	Non	Reflex	260.00	3.50°	-57.30°	Non
Reflex	164.00	1.20°	-57.90°	Non	Reflex	263.00	3.90°	-57.30°	Non
Reflex	167.00	0.80°	-57.90°	Non	Reflex	266.00	4.10°	-57.30°	Non
Reflex	170.00	0.50°	-57.80°	Non	Reflex	269.00	4.80°	-57.30°	Non
Reflex	173.00	1.60°	-57.80°	Non	Reflex	272.00	5.00°	-57.50°	Non
Reflex	176.00	4.60°	-57.80°	Oui	Reflex	275.00	4.50°	-57.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	278.00	2.40°	-57.40°	Non	Reflex	377.00	2.60°	-57.10°	Non
Reflex	281.00	2.40°	-57.40°	Non	Reflex	380.00	2.30°	-56.90°	Non
Reflex	284.00	0.80°	-57.50°	Oui	Reflex	383.00	4.00°	-56.80°	Non
Reflex	287.00	3.40°	-57.40°	Non	Reflex	386.00	1.40°	-56.80°	Non
Reflex	290.00	3.60°	-57.40°	Non	Reflex	389.00	1.00°	-56.70°	Non
Reflex	293.00	2.70°	-57.30°	Non	Reflex	392.00	2.80°	-56.80°	Non
Reflex	296.00	3.10°	-57.40°	Non	Reflex	395.00	3.30°	-56.80°	Non
Reflex	299.00	2.80°	-57.30°	Non	Reflex	398.00	2.80°	-56.70°	Non
Reflex	302.00	3.20°	-57.30°	Non	Reflex	401.00	6.00°	-56.80°	Oui
Reflex	305.00	2.40°	-57.40°	Non	Reflex	404.00	4.80°	-56.70°	Non
Reflex	308.00	3.30°	-57.20°	Non	Reflex	407.00	3.70°	-56.60°	Non
Reflex	311.00	4.40°	-57.30°	Non	Reflex	410.00	4.20°	-56.70°	Non
Reflex	314.00	5.40°	-57.30°	Oui	Reflex	413.00	4.20°	-56.70°	Non
Reflex	317.00	3.30°	-57.20°	Non	Reflex	416.00	4.30°	-56.60°	Non
Reflex	320.00	3.60°	-57.30°	Non	Reflex	419.00	5.50°	-56.70°	Non
Reflex	323.00	3.10°	-57.30°	Non	Reflex	422.00	5.80°	-56.70°	Non
Reflex	326.00	5.00°	-57.20°	Non	Reflex	425.00	4.50°	-56.70°	Non
Reflex	329.00	4.40°	-57.20°	Non	Reflex	428.00	8.70°	-57.30°	Oui
Reflex	332.00	3.30°	-57.30°	Non	Reflex	431.00	4.80°	-56.70°	Non
Reflex	335.00	3.70°	-57.30°	Non	Reflex	434.00	4.30°	-56.60°	Non
Reflex	338.00	9.40°	-57.20°	Oui	Reflex	437.00	2.50°	-56.60°	Non
Reflex	341.00	2.40°	-57.20°	Non	Reflex	440.00	5.00°	-56.80°	Non
Reflex	344.00	2.50°	-57.20°	Non	Reflex	443.00	4.80°	-56.60°	Non
Reflex	347.00	1.30°	-57.20°	Non	Reflex	446.00	1.90°	-56.40°	Non
Reflex	350.00	2.10°	-57.10°	Non	Reflex	449.00	2.90°	-56.50°	Non
Reflex	353.00	3.60°	-57.20°	Non	Reflex	452.00	2.80°	-56.50°	Non
Reflex	356.00	3.70°	-57.10°	Non	Reflex	455.00	3.20°	-56.50°	Non
Reflex	359.00	4.20°	-57.10°	Non	Reflex	458.00	3.80°	-56.50°	Non
Reflex	362.00	5.20°	-57.10°	Non	Reflex	461.00	4.10°	-56.50°	Non
Reflex	365.00	4.80°	-57.00°	Non	Reflex	464.00	3.60°	-56.50°	Non
Reflex	368.00	2.60°	-56.90°	Non	Reflex	467.00	5.40°	-56.50°	Oui
Reflex	371.00	3.00°	-57.00°	Non	Reflex	470.00	1.70°	-56.50°	Non
Reflex	374.00	1.60°	-57.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	4.10	MT Mort-terrain MT						
4.10	64.00	SY Syénite Syénite	4.10	5.50	D005501	1.40	0.022	0.022
			5.50	7.00	D005502	1.50	0.014	0.014
			7.00	8.50	D005503	1.50	0.012	0.012
			8.50	10.00	D005504	1.50	<0.005	0.001
			10.00	11.50	D005505	1.50	<0.005	0.001
			11.50	13.00	D005506	1.50	<0.005	0.001
			13.00	14.50	D005507	1.50	0.208	0.208
			14.50	16.00	D005508	1.50	<0.005	0.001
			16.00	17.50	D005509	1.50	<0.005	0.001
			17.50	19.00	D005510	1.50	<0.005	0.001
			19.00	20.50	D005511	1.50	0.012	0.012
			20.50	22.00	D005513	1.50	<0.005	0.001
			22.00	23.50	D005514	1.50	<0.005	0.001
			23.50	25.00	D005515	1.50	<0.005	0.001
			25.00	26.50	D005516	1.50	0.005	0.005
			26.50	28.00	D005517	1.50	0.005	0.005
			28.00	29.50	D005518	1.50	0.005	0.005
			29.50	31.00	D005519	1.50	<0.005	0.001
			31.00	32.50	D005520	1.50	0.005	0.005
			32.50	34.00	D005522	1.50	0.017	0.017
			34.00	35.50	D005523	1.50	0.017	0.017
			35.50	37.00	D005524	1.50	0.023	0.023
			37.00	38.50	D005525	1.50	0.036	0.036
			38.50	40.00	D005526	1.50	0.014	0.014
			40.00	41.50	D005527	1.50	0.094	0.094
			41.50	43.00	D005528	1.50	<0.005	0.001
			43.00	44.50	D005529	1.50	0.009	0.009
			44.50	46.00	D005530	1.50	0.517	0.517
			46.00	47.50	D005531	1.50	0.203	0.203
			47.50	49.00	D005532	1.50	0.021	0.021
			49.00	50.50	D005534	1.50	0.020	0.020

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
64.00	72.90	BA <b>Basalte</b> Basalte	50.50	52.00	D005535	1.50	0.025	3.25 3.73	0.025
			52.00	53.50	D005536	1.50	0.014		0.014
			53.50	55.00	D005537	1.50	0.025		0.025
			55.00	56.50	D005538	1.50	<0.005		0.001
			56.50	57.60	D005539	1.10	0.010		0.010
			57.60	59.00	D005540	1.40	3.330		3.250
			59.00	60.00	D005542	1.00	3.320		3.730
			60.00	61.00	D005543	1.00	2.670		2.670
			61.00	62.50	D005544	1.50	0.724		0.724
			62.50	64.00	D005545	1.50	1.795		1.795
			64.00	65.50	D005546	1.50	0.060		0.060
			65.50	67.00	D005547	1.50	<0.005		0.001
			67.00	68.00	D005548	1.00	<0.005		0.001
			68.00	69.00	D005549	1.00	<0.005		0.001
			72.90	470.70	SY <b>Syénite</b> Syénite	69.00	70.00		D005550
70.00	71.50	D005551				1.50	<0.005	0.001	
71.50	72.90	D005552				1.40	<0.005	0.001	
72.90	74.50	D005554				1.60	<0.005	0.001	
74.50	76.00	D005555				1.50	0.015	0.015	
76.00	77.50	D005556				1.50	0.011	0.011	
77.50	79.00	D005557				1.50	0.006	0.006	
79.00	80.50	D005558				1.50	0.017	0.017	
80.50	82.00	D005559				1.50	0.066	0.066	
82.00	83.50	D005560				1.50	0.006	0.006	
83.50	85.00	D005562				1.50	<0.005	0.001	
85.00	86.50	D005563				1.50	0.012	0.012	
86.50	88.00	D005564				1.50	0.009	0.009	
88.00	89.50	D005565				1.50	<0.005	0.001	
89.50	91.00	D005566				1.50	0.052	0.052	
91.00	92.50	D005567	1.50	<0.005	0.001				
92.50	94.00	D005568	1.50	0.008	0.008				
94.00	95.50	D005569	1.50	0.264	0.264				
95.50	97.00	D005570	1.50	0.016	0.016				

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	97.00	98.50	D005571	1.50	<0.005		0.001
	98.50	100.00	D005572	1.50	0.046		0.046
	100.00	101.50	D005574	1.50	0.032		0.032
	101.50	103.00	D005575	1.50	0.008		0.008
	103.00	104.50	D005576	1.50	<0.005		0.001
	104.50	106.00	D005577	1.50	0.006		0.006
	106.00	107.50	D005578	1.50	<0.005		0.001
	107.50	109.00	D005579	1.50	0.005		0.005
	109.00	110.50	D005580	1.50	<0.005		0.001
	110.50	112.00	D005582	1.50	0.074		0.074
	112.00	113.50	D005583	1.50	0.007		0.007
	113.50	115.00	D005584	1.50	0.439		0.439
	115.00	116.50	D005585	1.50	0.117		0.117
	116.50	118.00	D005586	1.50	0.074		0.074
	118.00	119.00	D005587	1.00	0.347		0.347
	119.00	120.00	D005588	1.00	0.013		0.013
	120.00	121.00	D005589	1.00	0.014		0.014
	121.00	122.50	D005590	1.50	1.020		1.020
	122.50	124.00	D005591	1.50	1.060		1.060
	124.00	125.50	D005592	1.50	0.314		0.314
	125.50	127.00	D005594	1.50	0.012		0.012
	127.00	128.50	D005595	1.50	0.158		0.158
	128.50	130.00	D005596	1.50	0.797		0.797
	130.00	131.50	D005597	1.50	0.062		0.062
	131.50	133.00	D005598	1.50	0.005		0.005
	133.00	134.50	D005599	1.50	0.006		0.006
	134.50	136.00	D005600	1.50	0.018		0.018
	136.00	137.50	D005602	1.50	0.042		0.042
	137.50	139.00	D005603	1.50	0.188		0.188
	139.00	140.50	D005604	1.50	0.072		0.072
	140.50	142.00	D005605	1.50	0.177		0.177
	142.00	143.50	D005606	1.50	0.128		0.128
	143.50	145.00	D005607	1.50	0.049		0.049



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	145.00	146.50	D005608	1.50	<0.005		0.001
	146.50	148.00	D005609	1.50	<0.005		0.001
	148.00	149.50	D005610	1.50	0.005		0.005
	149.50	151.00	D005611	1.50	<0.005		0.001
	151.00	152.50	D005612	1.50	<0.005		0.001
	152.50	154.00	D005614	1.50	0.005		0.005
	154.00	155.50	D005615	1.50	0.006		0.006
	155.50	157.00	D005616	1.50	0.051		0.051
	157.00	158.50	D005617	1.50	0.007		0.007
	158.50	160.00	D005618	1.50	0.006		0.006
	160.00	161.50	D005619	1.50	0.005		0.005
	161.50	163.00	D005620	1.50	<0.005		0.001
	163.00	164.50	D005622	1.50	<0.005		0.001
	164.50	166.00	D005623	1.50	0.017		0.017
	166.00	167.50	D005624	1.50	0.117		0.117
	167.50	169.00	D005625	1.50	0.010		0.010
	169.00	170.50	D005626	1.50	0.013		0.013
	170.50	172.00	D005627	1.50	0.007		0.007
	172.00	173.50	D005628	1.50	0.014		0.014
	173.50	175.00	D005629	1.50	0.063		0.063
	175.00	176.50	D005630	1.50	0.024		0.024
	176.50	178.00	D005631	1.50	0.005		0.005
	178.00	179.50	D005632	1.50	0.033		0.033
	179.50	181.00	D005634	1.50	0.175		0.175
	181.00	182.50	D005635	1.50	0.007		0.007
	182.50	184.00	D005636	1.50	0.088		0.088
	184.00	185.50	D005637	1.50	0.016		0.016
	185.50	187.00	D005638	1.50	0.119		0.119
	187.00	188.50	D005639	1.50	0.013		0.013
	188.50	190.00	D005640	1.50	2.280		2.280
	190.00	191.50	D005642	1.50	1.865		1.865
	191.50	193.00	D005643	1.50	0.033		0.033
	193.00	194.50	D005644	1.50	0.011		0.011

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	194.50	196.00	D005645	1.50	0.012		0.012
	196.00	197.50	D005646	1.50	0.016		0.016
	197.50	199.00	D005647	1.50	0.012		0.012
	199.00	200.50	D005648	1.50	0.010		0.010
	200.50	202.00	D005649	1.50	0.021		0.021
	202.00	203.50	D005650	1.50	0.008		0.008
	203.50	205.00	D005651	1.50	0.011		0.011
	205.00	206.50	D005652	1.50	0.010		0.010
	206.50	208.00	D005654	1.50	0.010		0.010
	208.00	209.50	D005655	1.50	0.023		0.023
	209.50	211.00	D005656	1.50	<0.005		0.001
	211.00	212.50	D005657	1.50	0.015		0.015
	212.50	214.00	D005658	1.50	0.010		0.010
	214.00	215.50	D005659	1.50	0.116		0.116
	215.50	217.00	D005660	1.50	0.089		0.089
	217.00	218.50	D005662	1.50	0.246		0.246
	218.50	220.00	D005663	1.50	0.072		0.072
	220.00	221.50	D005664	1.50	0.016		0.016
	221.50	223.00	D005665	1.50	0.448		0.448
	223.00	224.50	D005666	1.50	0.274		0.274
	224.50	226.00	D005667	1.50	0.126		0.126
	226.00	227.50	D005668	1.50	0.030		0.030
	227.50	229.00	D005669	1.50	<0.005		0.001
	229.00	230.50	D005670	1.50	0.008		0.008
	230.50	232.00	D005671	1.50	<0.005		0.001
	232.00	233.50	D005672	1.50	<0.005		0.001
	233.50	235.00	D005674	1.50	<0.005		0.001
	235.00	236.50	D005675	1.50	<0.005		0.001
	236.50	238.00	D005676	1.50	0.007		0.007
	238.00	239.50	D005677	1.50	<0.005		0.001
	239.50	241.00	D005678	1.50	<0.005		0.001
	241.00	242.50	D005679	1.50	1.310		1.310
	242.50	244.00	D005680	1.50	0.714		0.714

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	244.00	245.50	D005682	1.50	0.024		0.024
	245.50	247.00	D005683	1.50	0.026		0.026
	247.00	248.50	D005684	1.50	0.133		0.133
	248.50	250.00	D005685	1.50	0.394		0.394
	250.00	251.50	D005686	1.50	<0.005		0.001
	251.50	253.00	D005687	1.50	1.030		1.030
	253.00	254.50	D005688	1.50	1.495		1.495
	254.50	256.00	D005689	1.50	0.569		0.569
	256.00	257.50	D005690	1.50	0.051		0.051
	257.50	259.00	D005691	1.50	0.090		0.090
	259.00	260.50	D005692	1.50	0.017		0.017
	260.50	262.00	D005694	1.50	0.236		0.236
	262.00	263.50	D005695	1.50	0.850		0.850
	263.50	264.60	D005696	1.10	1.785		1.785
	264.60	266.00	D005697	1.40	0.112		0.112
	266.00	267.50	D005698	1.50	0.188		0.188
	267.50	269.00	D005699	1.50	0.072		0.072
	269.00	270.50	D005700	1.50	0.047		0.047
	270.50	272.00	D005702	1.50	1.120		1.120
	272.00	273.50	D005703	1.50	0.706		0.706
	273.50	275.20	D005704	1.70	0.132		0.132
	275.20	276.90	D005705	1.70	0.027		0.027
	276.90	278.50	D005706	1.60	<0.005		0.001
	278.50	280.00	D005707	1.50	0.135		0.135
	280.00	281.50	D005708	1.50	<0.005		0.001
	281.50	283.00	D005709	1.50	0.013		0.013
	283.00	284.50	D005710	1.50	0.954		0.954
	284.50	286.00	D005711	1.50	0.268		0.268
	286.00	287.50	D005712	1.50	0.127		0.127
	287.50	289.00	D005714	1.50	0.013		0.013
	289.00	290.50	D005715	1.50	0.006		0.006
	290.50	292.00	D005716	1.50	<0.005		0.001
	292.00	293.50	D005717	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	293.50	295.00	D005718	1.50	<0.005		0.001
	295.00	296.50	D005719	1.50	0.016		0.016
	296.50	298.00	D005720	1.50	0.029		0.029
	298.00	299.00	D005722	1.00	<0.005		0.001
	299.00	300.00	D005723	1.00	0.013		0.013
	300.00	301.50	D005724	1.50	0.076		0.076
	301.50	302.50	D005725	1.00	0.050		0.050
	302.50	304.00	D005726	1.50	0.007		0.007
	304.00	305.50	D005727	1.50	<0.005		0.001
	305.50	307.00	D005728	1.50	0.015		0.015
	307.00	308.50	D005729	1.50	<0.005		0.001
	308.50	310.00	D005730	1.50	0.088		0.088
	310.00	311.50	D005731	1.50	<0.005		0.001
	311.50	313.00	D005732	1.50	0.239		0.239
	313.00	314.50	D005734	1.50	0.009		0.009
	314.50	316.00	D005735	1.50	<0.005		0.001
	316.00	317.50	D005736	1.50	0.030		0.030
	317.50	319.00	D005737	1.50	0.042		0.042
	319.00	320.50	D005738	1.50	0.027		0.027
	320.50	322.00	D005739	1.50	0.009		0.009
	322.00	323.50	D005740	1.50	0.077		0.077
	323.50	325.00	D005742	1.50	0.419		0.419
	325.00	326.50	D005743	1.50	<0.005		0.001
	326.50	328.00	D005744	1.50	<0.005		0.001
	328.00	329.50	D005745	1.50	0.011		0.011
	329.50	331.00	D005746	1.50	<0.005		0.001
	331.00	332.50	D005747	1.50	0.011		0.011
	332.50	334.00	D005748	1.50	0.009		0.009
	334.00	335.00	D005749	1.00	0.008		0.008
	335.00	336.00	D005750	1.00	0.128		0.128
	336.00	337.30	D005751	1.30	0.080		0.080
	337.30	338.50	D005752	1.20	0.131		0.131
	338.50	340.00	D005754	1.50	0.023		0.023

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	340.00	341.50	D005755	1.50	<0.005		0.001
	341.50	343.00	D005756	1.50	0.033		0.033
	343.00	344.50	D005757	1.50	<0.005		0.001
	344.50	346.00	D005758	1.50	0.022		0.022
	346.00	347.50	D005759	1.50	0.093		0.093
	347.50	349.00	D005760	1.50	<0.005		0.001
	349.00	350.30	D005762	1.30	<0.005		0.001
	350.30	352.00	D005763	1.70	0.005		0.005
	352.00	353.50	D005764	1.50	0.006		0.006
	353.50	355.00	D005765	1.50	<0.005		0.001
	355.00	356.50	D005766	1.50	<0.005		0.001
	356.50	358.00	D005767	1.50	0.012		0.012
	358.00	359.50	D005768	1.50	0.008		0.008
	359.50	361.00	D005769	1.50	0.040		0.040
	361.00	362.50	D005770	1.50	0.068		0.068
	362.50	364.00	D005771	1.50	<0.005		0.001
	364.00	365.50	D005772	1.50	<0.005		0.001
	365.50	367.00	D005774	1.50	<0.005		0.001
	367.00	368.50	D005775	1.50	<0.005		0.001
	368.50	370.00	D005776	1.50	<0.005		0.001
	370.00	371.50	D005777	1.50	<0.005		0.001
	371.50	373.00	D005778	1.50	<0.005		0.001
	373.00	374.50	D005779	1.50	<0.005		0.001
	374.50	376.00	D005780	1.50	<0.005		0.001
	376.00	377.00	D005782	1.00	0.006		0.006
	377.00	378.50	D005783	1.50	0.124		0.124
	378.50	380.00	D005784	1.50	0.341		0.341
	380.00	381.00	D005785	1.00	<0.005		0.001
	381.00	382.00	D005786	1.00	<0.005		0.001
	382.00	383.50	D005787	1.50	0.012		0.012
	383.50	385.00	D005788	1.50	<0.005		0.001
	385.00	386.50	D005789	1.50	0.034		0.034
	386.50	388.00	D005790	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	388.00	389.50	D005791	1.50	0.007		0.007
	389.50	391.00	D005792	1.50	0.403		0.403
	391.00	392.50	D005794	1.50	0.513		0.513
	392.50	394.00	D005795	1.50	0.174		0.174
	394.00	395.50	D005796	1.50	0.009		0.009
	395.50	397.00	D005797	1.50	0.007		0.007
	397.00	398.50	D005798	1.50	0.034		0.034
	398.50	400.00	D005799	1.50	0.007		0.007
	400.00	401.50	D005800	1.50	0.009		0.009
	401.50	403.00	D005802	1.50	0.007		0.007
	403.00	404.50	D005803	1.50	0.018		0.018
	404.50	406.00	D005804	1.50	0.005		0.005
	406.00	407.50	D005805	1.50	<0.005		0.001
	407.50	408.50	D005806	1.00	<0.005		0.001
	408.50	409.50	D005807	1.00	<0.005		0.001
	409.50	411.00	D005808	1.50	<0.005		0.001
	411.00	412.50	D005809	1.50	<0.005		0.001
	412.50	414.20	D005810	1.70	<0.005		0.001
	414.20	415.50	D005811	1.30	<0.005		0.001
	415.50	417.00	D005812	1.50	<0.005		0.001
	417.00	418.50	D005814	1.50	<0.005		0.001
	418.50	420.00	D005815	1.50	<0.005		0.001
	420.00	421.50	D005816	1.50	<0.005		0.001
	421.50	423.00	D005817	1.50	<0.005		0.001
	423.00	424.50	D005818	1.50	<0.005		0.001
	424.50	426.00	D005819	1.50	<0.005		0.001
	426.00	427.50	D005820	1.50	0.023		0.023
	427.50	429.00	D005822	1.50	<0.005		0.001
	429.00	430.50	D005823	1.50	<0.005		0.001
	430.50	432.00	D005824	1.50	<0.005		0.001
	432.00	433.50	D005825	1.50	<0.005		0.001
	433.50	435.00	D005826	1.50	0.161		0.161
	435.00	436.50	D005827	1.50	0.398		0.398

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	436.50	438.00	D005828	1.50	2.810		2.810
	438.00	439.50	D005829	1.50	0.515		0.515
	439.50	441.00	D005830	1.50	0.068		0.068
	441.00	442.50	D005831	1.50	0.089		0.089
	442.50	444.00	D005832	1.50	0.078		0.078
	444.00	445.50	D005834	1.50	0.851		0.851
	445.50	447.00	D005835	1.50	0.634		0.634
	447.00	448.50	D005836	1.50	0.555		0.555
	448.50	450.00	D005837	1.50	0.336		0.336
	450.00	451.50	D005838	1.50	0.262		0.262
	451.50	453.00	D005839	1.50	1.540		1.540
	453.00	454.50	D005840	1.50	0.240		0.240
	454.50	456.00	D005842	1.50	0.574		0.574
	456.00	457.50	D005843	1.50	0.624		0.624
	457.50	459.00	D005844	1.50	0.323		0.323
	459.00	460.50	D005845	1.50	0.564		0.564
	460.50	462.00	D005846	1.50	0.458		0.458
	462.00	463.50	D005847	1.50	0.280		0.280
	463.50	465.00	D005848	1.50	0.598		0.598
	465.00	466.50	D005849	1.50	0.267		0.267
	466.50	468.00	D005850	1.50	0.443		0.443
	468.00	469.50	D005851	1.50	0.059		0.059
	469.50	470.70	D005852	1.20	0.384		0.384
470.70	Fin du sondage Nombre d'échantillons : 318 Nombre d'échantillons QAQC : 34 Longueur totale échantillonnée : 466.60						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
19.00	20.50	D005512	A3	1.50	0.590	0.590
31.00	32.50	D005521	D005520	1.50	0.007	0.007
47.50	49.00	D005533	M1	1.50	<0.005	0.001
57.60	59.00	D005541	D005540	1.40	3.490	3.570
71.50	72.90	D005553	H	1.40	1.000	1.000
82.00	83.50	D005561	D005560	1.50	0.005	0.005
98.50	100.00	D005573	M1	1.50	<0.005	0.001
109.00	110.50	D005581	D005580	1.50	0.006	0.006
124.00	125.50	D005593	B4	1.50	2.560	2.560
134.50	136.00	D005601	D005600	1.50	0.008	0.008
151.00	152.50	D005613	M1	1.50	<0.005	0.001
161.50	163.00	D005621	D005620	1.50	<0.005	0.001
178.00	179.50	D005633	F2	1.50	8.050	8.060
188.50	190.00	D005641	D005640	1.50	2.230	2.230
205.00	206.50	D005653	M1	1.50	0.006	0.006
215.50	217.00	D005661	D005660	1.50	0.103	0.103
232.00	233.50	D005673	D2	1.50	0.885	0.885
242.50	244.00	D005681	D005680	1.50	0.697	0.697
259.00	260.50	D005693	M1	1.50	<0.005	0.001
269.00	270.50	D005701	D005700	1.50	0.047	0.047
286.00	287.50	D005713	A3	1.50	0.641	0.641
296.50	298.00	D005721	D005720	1.50	0.023	0.023
311.50	313.00	D005733	M1	1.50	<0.005	0.001
322.00	323.50	D005741	D005740	1.50	0.054	0.054
337.30	338.50	D005753	H	1.20	0.993	0.993
347.50	349.00	D005761	D005760	1.50	<0.005	0.001
364.00	365.50	D005773	M1	1.50	<0.005	0.001
374.50	376.00	D005781	D005780	1.50	<0.005	0.001
389.50	391.00	D005793	G2	1.50	4.160	4.410
400.00	401.50	D005801	D005800	1.50	0.017	0.017
415.50	417.00	D005813	M1	1.50	<0.005	0.001
426.00	427.50	D005821	D005820	1.50	<0.005	0.001
442.50	444.00	D005833	F2	1.50	8.760	8.510



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
453.00	454.50	D005841	D005840	1.50	0.221	0.221

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-123**

Titre minier :

Section :                      630900

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          Gilles. Kamta

Du :                      2010-03-04

Date de description :

Au :                     2010-03-13

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            454.60 m

Est	630 899.9
Nord	5 374 359.7
Élévation	314.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	1.80°	-58.70°	Non
Reflex	5.00	359.80°	-58.40°	Non
Reflex	8.00	359.60°	-58.40°	Non
Reflex	11.00	1.90°	-60.70°	Non
Reflex	14.00	0.90°	-59.70°	Non
Reflex	17.00	359.80°	-58.30°	Non
Reflex	20.00	9.00°	-66.00°	Oui
Reflex	23.00	359.70°	-58.30°	Non
Reflex	26.00	359.70°	-58.20°	Non
Reflex	29.00	359.70°	-58.20°	Non
Reflex	32.00	358.40°	-58.20°	Non
Reflex	35.00	359.80°	-58.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	360.00°	-58.10°	Non
Reflex	41.00	357.40°	-58.10°	Non
Reflex	44.00	359.70°	-58.10°	Non
Reflex	47.00	358.70°	-58.00°	Non
Reflex	50.00	358.70°	-58.00°	Non
Reflex	53.00	358.60°	-57.90°	Non
Reflex	56.00	358.50°	-57.90°	Non
Reflex	59.00	358.40°	-57.90°	Non
Reflex	62.00	358.80°	-57.80°	Non
Reflex	65.00	358.50°	-57.70°	Non
Reflex	68.00	358.40°	-57.70°	Non
Reflex	71.00	358.20°	-57.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	358.00°	-57.60°	Non	Reflex	173.00	356.50°	-56.50°	Non
Reflex	77.00	358.30°	-57.60°	Non	Reflex	176.00	357.80°	-56.40°	Non
Reflex	80.00	358.50°	-57.80°	Non	Reflex	179.00	1.10°	-56.50°	Oui
Reflex	83.00	357.60°	-57.50°	Non	Reflex	182.00	357.50°	-56.50°	Non
Reflex	86.00	357.50°	-57.50°	Non	Reflex	185.00	1.30°	-56.50°	Non
Reflex	89.00	358.20°	-57.50°	Non	Reflex	188.00	0.20°	-56.50°	Non
Reflex	92.00	358.50°	-57.50°	Non	Reflex	191.00	358.30°	-56.50°	Non
Reflex	95.00	357.80°	-57.50°	Non	Reflex	194.00	356.80°	-56.50°	Non
Reflex	98.00	357.60°	-57.50°	Non	Reflex	197.00	356.40°	-56.40°	Non
Reflex	101.00	357.60°	-57.50°	Non	Reflex	200.00	357.30°	-56.40°	Non
Reflex	104.00	357.10°	-57.40°	Non	Reflex	203.00	357.80°	-56.40°	Non
Reflex	107.00	356.50°	-57.40°	Non	Reflex	206.00	359.50°	-56.30°	Non
Reflex	110.00	357.20°	-57.40°	Non	Reflex	209.00	358.00°	-56.30°	Non
Reflex	113.00	357.30°	-57.30°	Non	Reflex	212.00	359.10°	-56.30°	Non
Reflex	116.00	357.40°	-57.30°	Non	Reflex	215.00	358.90°	-56.30°	Non
Reflex	119.00	354.70°	-52.30°	Non	Reflex	218.00	358.80°	-54.30°	Non
Reflex	122.00	357.80°	-57.20°	Non	Reflex	221.00	356.70°	-56.20°	Oui
Reflex	125.00	358.10°	-57.20°	Non	Reflex	224.00	359.50°	-56.20°	Non
Reflex	128.00	358.00°	-57.10°	Non	Reflex	227.00	357.80°	-56.20°	Non
Reflex	131.00	358.30°	-57.10°	Non	Reflex	230.00	357.30°	-56.20°	Non
Reflex	134.00	358.60°	-57.20°	Non	Reflex	233.00	357.90°	-56.20°	Non
Reflex	137.00	358.50°	-57.10°	Non	Reflex	236.00	358.20°	-56.10°	Non
Reflex	140.00	0.50°	-57.10°	Oui	Reflex	239.00	357.90°	-56.10°	Non
Reflex	143.00	358.90°	-57.00°	Non	Reflex	242.00	357.10°	-56.00°	Non
Reflex	146.00	358.90°	-56.90°	Non	Reflex	245.00	352.50°	-56.00°	Oui
Reflex	149.00	358.30°	-56.70°	Non	Reflex	248.00	358.90°	-56.00°	Non
Reflex	152.00	358.50°	-56.70°	Non	Reflex	251.00	356.30°	-56.00°	Non
Reflex	155.00	358.90°	-56.60°	Non	Reflex	254.00	358.30°	-56.10°	Non
Reflex	158.00	358.60°	-56.60°	Non	Reflex	257.00	358.60°	-56.10°	Non
Reflex	161.00	357.90°	-56.60°	Non	Reflex	260.00	358.30°	-56.00°	Non
Reflex	164.00	358.10°	-56.60°	Non	Reflex	263.00	358.80°	-56.00°	Non
Reflex	167.00	358.90°	-56.50°	Non	Reflex	266.00	359.20°	-56.00°	Non
Reflex	170.00	357.50°	-56.50°	Non	Reflex	269.00	359.90°	-56.00°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	358.70°	-56.00°	Non	Reflex	371.00	359.60°	-55.00°	Non
Reflex	275.00	359.60°	-55.90°	Non	Reflex	374.00	0.00°	-55.00°	Non
Reflex	278.00	358.30°	-55.90°	Non	Reflex	377.00	355.10°	-55.00°	Oui
Reflex	281.00	357.30°	-55.90°	Non	Reflex	380.00	357.20°	-55.00°	Non
Reflex	284.00	358.50°	-55.80°	Non	Reflex	383.00	358.20°	-55.00°	Non
Reflex	287.00	358.10°	-55.60°	Non	Reflex	386.00	358.30°	-55.00°	Non
Reflex	290.00	359.00°	-55.60°	Non	Reflex	389.00	357.70°	-55.00°	Non
Reflex	293.00	358.50°	-55.70°	Non	Reflex	392.00	357.90°	-55.00°	Non
Reflex	296.00	356.90°	-55.60°	Oui	Reflex	395.00	358.20°	-54.90°	Non
Reflex	299.00	359.50°	-55.60°	Non	Reflex	398.00	358.30°	-54.80°	Non
Reflex	302.00	358.40°	-55.60°	Non	Reflex	401.00	358.60°	-54.90°	Non
Reflex	305.00	359.10°	-55.60°	Non	Reflex	404.00	359.20°	-54.80°	Non
Reflex	308.00	357.30°	-55.50°	Non	Reflex	407.00	359.40°	-54.70°	Non
Reflex	311.00	357.10°	-55.60°	Non	Reflex	410.00	359.30°	-54.40°	Non
Reflex	314.00	358.90°	-55.50°	Non	Reflex	413.00	359.30°	-54.30°	Non
Reflex	317.00	358.80°	-55.50°	Non	Reflex	416.00	359.10°	-54.20°	Non
Reflex	320.00	356.90°	-55.50°	Non	Reflex	419.00	359.00°	-54.20°	Non
Reflex	323.00	357.70°	-55.40°	Non	Reflex	422.00	359.10°	-54.20°	Non
Reflex	326.00	358.30°	-55.40°	Non	Reflex	425.00	358.90°	-54.10°	Non
Reflex	329.00	357.70°	-55.40°	Non	Reflex	428.00	358.90°	-54.10°	Non
Reflex	332.00	358.60°	-55.40°	Non	Reflex	431.00	358.80°	-54.00°	Non
Reflex	335.00	358.00°	-55.40°	Non	Reflex	434.00	358.80°	-53.90°	Non
Reflex	338.00	358.20°	-55.30°	Non	Reflex	437.00	358.50°	-52.60°	Non
Reflex	341.00	354.10°	-55.10°	Oui					
Reflex	344.00	357.30°	-55.10°	Non					
Reflex	347.00	358.10°	-55.10°	Non					
Reflex	350.00	357.60°	-55.10°	Non					
Reflex	353.00	355.30°	-55.00°	Oui					
Reflex	356.00	357.90°	-55.00°	Non					
Reflex	359.00	358.60°	-55.00°	Non					
Reflex	362.00	357.20°	-55.00°	Non					
Reflex	365.00	358.80°	-55.00°	Non					
Reflex	368.00	358.80°	-55.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.90	MT <b>Mort-terrain</b> MT						
1.90	442.60	SY <b>Syénite</b> Syénite rosé à rougeâtre avec passages jaune vert, localement phénocristaux de feldspaths automorphe 0.2-2 cm svt zonées et/ ou épidotisé, passages cisailés, passages bréchiés à sub bréchiés avec des fragments anguleux mm-cm, qlq vacuoles mm, qlq veines 1-20 cm, veinules et cheveux de quartz et carbonates, localement altération en calcite, séricitisation, oxyde de carbonates rouge ocre, biotite, localement magnétique, PY automorphe et fine irrég diss	1.90	3.00	D000937	1.10	<0.005	0.001
			3.00	4.00	D000938	1.00	<0.005	0.001
			4.00	5.50	D000939	1.50	<0.005	0.001
			5.50	7.00	D000940	1.50	<0.005	0.001
			7.00	8.50	D000941	1.50	<0.005	0.001
			8.50	10.00	D000942	1.50	<0.005	0.001
			10.00	11.50	D000943	1.50	<0.005	0.001
			11.50	13.00	D000944	1.50	0.012	0.012
			13.00	14.50	D000945	1.50	<0.005	0.001
			14.50	16.00	D000947	1.50	0.022	0.022
			16.00	17.50	D000948	1.50	0.077	0.077
			17.50	19.00	D000949	1.50	0.101	0.101
			19.00	20.50	D000950	1.50	0.005	0.005
			20.50	22.00	D000951	1.50	<0.005	0.001
			22.00	23.50	D000952	1.50	0.005	0.005
			23.50	25.00	D000953	1.50	0.014	0.014
			25.00	26.50	D000954	1.50	0.005	0.005
			26.50	28.00	D000955	1.50	<0.005	0.001
			28.00	29.50	D000957	1.50	0.011	0.011
			29.50	31.00	D000958	1.50	0.026	0.026
			31.00	32.50	D000959	1.50	0.016	0.016
			32.50	34.00	D000960	1.50	0.027	0.027
			34.00	35.50	D000961	1.50	0.035	0.035
			35.50	37.00	D000962	1.50	0.108	0.108
			37.00	38.50	D000963	1.50	0.033	0.033
			38.50	40.00	D000964	1.50	0.074	0.074
			40.00	41.50	D000965	1.50	0.026	0.026
			41.50	43.00	D000967	1.50	0.125	0.125
			43.00	44.50	D000968	1.50	0.187	0.187
			44.50	46.00	D000969	1.50	0.008	0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
56.00	62.00	SY; BRI <b>Syénite; Brèche intrusive</b> Syénite porphyrique bréchique à sub bréchique, fragments mm-cm sub arrondi ou anguleus grisâtre à jaunâtre, légèrement rosé entre 62-veinules et cheveux en reseaux ou 30-40° ac, séricite, biotite, K+, PY fine 0.5- 0.8%	46.00	47.50	D000970	1.50	0.053	5.70	0.053
			47.50	49.00	D000971	1.50	0.515		0.515
			49.00	50.50	D000972	1.50	0.330		0.330
			50.50	52.00	D000973	1.50	0.012		0.012
			52.00	53.50	D000974	1.50	0.038		0.038
			53.50	55.00	D000975	1.50	0.063		0.063
			55.00	56.00	D000977	1.00	0.080		0.080
			56.00	57.50	D000978	1.50	2.780		2.780
			57.50	59.00	D000979	1.50	5.540		5.700
			59.00	60.50	D000980	1.50	1.015		1.015
			60.50	62.00	D000981	1.50	1.690	1.690	
			62.00	63.50	D000982	1.50	1.080	1.080	
			63.50	65.00	D000983	1.50	0.328	0.328	
			65.00	66.50	D000984	1.50	0.084	0.084	
			66.50	68.00	D000985	1.50	0.023	0.023	
			68.00	69.50	D000987	1.50	0.017	0.017	
			69.50	71.00	D000988	1.50	0.005	0.005	
			71.00	72.50	D000989	1.50	0.034	0.034	
			72.50	74.00	D000990	1.50	0.016	0.016	
			74.00	75.50	D000991	1.50	0.031	0.031	
			75.50	77.00	D000992	1.50	0.293	0.293	
			77.00	78.50	D000993	1.50	0.101	0.101	
			78.50	80.00	D000994	1.50	1.560	1.560	
			80.00	81.50	D000995	1.50	1.500	1.500	
			81.50	83.00	D000997	1.50	3.080	3.080	
83.00	84.50	D000998	1.50	1.395	1.395				
84.50	86.00	D000999	1.50	2.650	2.650				
86.00	87.50	D001000	1.50	0.401	0.401				
87.50	89.00	D001001	1.50	0.256	0.256				
89.00	90.50	D001002	1.50	0.289	0.289				
90.50	92.00	D001003	1.50	0.320	0.320				
92.00	93.50	D001004	1.50	0.215	0.215				
93.50	95.00	D001005	1.50	0.050	0.050				



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		cisaillement 30° ac	142.30	143.50	D001043	1.20	<0.005	0.001
			143.50	145.00	D001044	1.50	<0.005	0.001
144.40	144.45	FAI	145.00	146.40	D001045	1.40	<0.005	0.001
		<b>Faille 60°</b>	146.40	147.70	D001047	1.30	<0.005	0.001
		faille 60° ac boue blanchâtre	147.70	149.00	D001048	1.30	0.030	0.030
			149.00	150.50	D001049	1.50	<0.005	0.001
			150.50	152.00	D001050	1.50	<0.005	0.001
			152.00	153.50	D001051	1.50	<0.005	0.001
			153.50	154.60	D001052	1.10	0.185	0.185
			154.60	155.60	D001053	1.00	<0.005	0.001
			155.60	157.00	D001054	1.40	<0.005	0.001
			157.00	158.40	D001055	1.40	0.023	0.023
			158.40	160.00	D001057	1.60	0.007	0.007
			160.00	161.50	D001058	1.50	<0.005	0.001
			161.50	163.00	D001059	1.50	<0.005	0.001
			163.00	164.50	D001060	1.50	<0.005	0.001
			164.50	166.00	D001061	1.50	<0.005	0.001
			166.00	167.50	D001062	1.50	<0.005	0.001
			167.50	169.00	D001063	1.50	<0.005	0.001
			169.00	170.50	D001064	1.50	<0.005	0.001
			170.50	172.00	D001065	1.50	<0.005	0.001
			172.00	173.50	D001067	1.50	<0.005	0.001
			173.50	175.00	D001068	1.50	<0.005	0.001
			175.00	176.50	D001069	1.50	0.006	0.006
			176.50	178.00	D001070	1.50	0.030	0.030
			178.00	179.50	D001071	1.50	0.039	0.039
			179.50	181.00	D001072	1.50	<0.005	0.001
			181.00	182.50	D001073	1.50	<0.005	0.001
			182.50	184.00	D001074	1.50	0.022	0.022
			184.00	185.60	D001075	1.60	0.095	0.095
185.60	187.60	SY; FIN	185.60	186.60	D001077	1.00	0.231	0.231
		<b>Syénite; Grains fins</b>	186.60	187.60	D001078	1.00	0.222	0.222
		syénite à grains fin, phénocristaux mm étiré, cisailé, veines deQZ cm carbonaté, chlorite, epidote et séricite, contact difus	187.60	189.00	D001079	1.40	0.107	0.107



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
205.00	210.40	SY; FIN; RUB <b>Syénite; Grains fins; Rubané</b> syénite à grains fin cisailé, localement rubané, qlq phénocristaux mm, veines de QZ 1-10-35 cm carbonâtées, séricite, chlorite	189.00	190.50	D001080	1.50	0.007		0.007
			190.50	192.00	D001081	1.50	<0.005		0.001
			192.00	193.50	D001082	1.50	0.102		0.102
			193.50	195.00	D001083	1.50	<0.005		0.001
			195.00	196.50	D001084	1.50	0.030		0.030
			196.50	198.00	D001085	1.50	0.064		0.064
			198.00	199.50	D001087	1.50	0.035		0.035
			199.50	201.00	D001088	1.50	<0.005		0.001
			201.00	202.50	D001089	1.50	0.087		0.087
			202.50	204.00	D001090	1.50	<0.005		0.001
			204.00	205.00	D001091	1.00	0.008		0.008
			205.00	206.50	D001092	1.50	0.110		0.110
			206.50	208.00	D001093	1.50	0.227		0.227
			208.00	209.40	D001094	1.40	0.338		0.338
			209.40	210.40	D001095	1.00	0.651		0.651
			210.40	212.00	D001097	1.60	0.024		0.024
			212.00	213.50	D001098	1.50	0.054		0.054
			213.50	215.00	D001099	1.50	0.157		0.157
			215.00	216.50	D001100	1.50	<0.005		0.001
			216.50	218.00	D001101	1.50	0.017		0.017
218.00	219.50	D001102	1.50	0.005		0.005			
219.50	221.00	D001103	1.50	0.005		0.005			
221.00	222.50	D001104	1.50	0.005		0.005			
222.50	224.00	D001105	1.50	<0.005		0.001			
224.00	225.50	D001107	1.50	0.081		0.081			
225.50	227.00	D001108	1.50	<0.005		0.001			
227.00	228.50	D001109	1.50	0.009		0.009			
228.50	230.00	D001110	1.50	0.006		0.006			
230.00	231.20	D001111	1.20	<0.005		0.001			
231.20	233.50	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite séricitisé cisailé, phénocristaux 0.2-0.4 cm, localement étré suivant le plan de cisaillement 40-50° ac PY fine diss	231.20	232.50	D001112	1.30	0.422		0.422
			232.50	233.50	D001113	1.00	0.005		0.005
			233.50	235.00	D001114	1.50	0.034		0.034
			235.00	236.50	D001115	1.50	0.074		0.074

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
239.60	240.30	SY; FIN <b>Syénite; Grains fins</b> altération en séricite, qlq phénocristaux chloritisés étirés 30° ac	236.50	238.00	D001117	1.50	0.006		0.006
			238.00	239.60	D001118	1.60	<0.005		0.001
			239.60	240.60	D001119	1.00	<0.005		0.001
			240.60	241.60	D001120	1.00	0.240		0.240
			241.60	243.00	D001121	1.40	0.204		0.204
243.00	245.60	SY; FIN; RUB <b>Syénite 40°; Grains fins; Rubané</b> localement schisteuse avec lentilles de carbonâtes, altération en séricite et calcite, PY fine irrég dis	243.00	244.50	D001122	1.50	1.930		1.930
			244.50	245.60	D001123	1.10	0.055		0.055
			245.60	247.00	D001124	1.40	<0.005		0.001
			247.00	248.50	D001125	1.50	0.050		0.050
			248.50	250.00	D001127	1.50	0.072		0.072
			250.00	251.00	D001128	1.00	0.033		0.033
			251.00	252.00	D001129	1.00	0.123		0.123
			252.00	253.50	D001130	1.50	0.736		0.736
252.00	256.00	SY; FIN <b>Syénite 80°; Grains fins</b> massive localement altéré et silice et bréchiq, schisteuse, altération en calcite et séricite	253.50	255.00	D001131	1.50	1.015		1.015
			255.00	256.00	D001132	1.00	2.280		2.280
			256.00	257.50	D001133	1.50	0.138		0.138
			257.50	259.00	D001134	1.50	0.017		0.017
			259.00	260.50	D001135	1.50	0.097		0.097
			260.50	262.00	D001137	1.50	0.191		0.191
			262.00	263.50	D001138	1.50	0.006		0.006
			263.50	265.00	D001139	1.50	<0.005		0.001
			265.00	266.50	D001140	1.50	<0.005		0.001
			266.50	268.00	D001141	1.50	0.045		0.045
			268.00	269.50	D001142	1.50	0.014		0.014
			269.50	271.00	D001143	1.50	0.039		0.039
			271.00	272.50	D001144	1.50	0.014		0.014
			272.50	274.00	D001145	1.50	<0.005		0.001
			274.00	275.50	D001147	1.50	<0.005		0.001
275.50	277.00	D001148	1.50	<0.005		0.001			
277.00	278.50	D001149	1.50	<0.005		0.001			
278.50	280.00	D001150	1.50	<0.005		0.001			
280.00	281.50	D001151	1.50	<0.005		0.001			
281.50	283.00	D001152	1.50	0.032		0.032			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
294.40	295.60	SY; RUB; FIN <b>Syénite; Rubané; Grains fins</b> altération en calcite et séricite, localement pseudo schistosité,	283.00	284.50	D001153	1.50	0.143		0.143
			284.50	286.00	D001154	1.50	0.046		0.046
			286.00	287.50	D001155	1.50	0.036		0.036
			287.50	289.00	D001157	1.50	0.157		0.157
			289.00	290.50	D001158	1.50	0.089		0.089
			290.50	292.00	D001159	1.50	<0.005		0.001
			292.00	293.40	D001160	1.40	0.156		0.156
			293.40	294.40	D001161	1.00	0.089		0.089
			294.40	295.60	D001162	1.20	0.448		0.448
			295.60	297.00	D001163	1.40	<0.005		0.001
			297.00	298.50	D001164	1.50	<0.005		0.001
			298.50	300.00	D001165	1.50	<0.005		0.001
			300.00	301.50	D001167	1.50	<0.005		0.001
			301.50	303.00	D001168	1.50	<0.005		0.001
			303.00	304.50	D001169	1.50	<0.005		0.001
			304.50	305.50	D001170	1.00	<0.005		0.001
			305.50	307.00	D001171	1.50	<0.005		0.001
			307.00	308.50	D001172	1.50	<0.005		0.001
			308.50	310.00	D001173	1.50	<0.005		0.001
			310.00	311.50	D001174	1.50	<0.005		0.001
			311.50	313.00	D001175	1.50	<0.005		0.001
			313.00	314.50	D001177	1.50	<0.005		0.001
			314.50	316.00	D001178	1.50	<0.005		0.001
			316.00	317.50	D001179	1.50	<0.005		0.001
			317.50	319.00	D001180	1.50	<0.005		0.001
			319.00	320.50	D001181	1.50	<0.005		0.001
			320.50	322.00	D001182	1.50	<0.005		0.001
			322.00	323.50	D001183	1.50	<0.005		0.001
323.50	325.00	D001184	1.50	<0.005		0.001			
325.00	326.50	D001185	1.50	<0.005		0.001			
326.50	328.00	D001187	1.50	<0.005		0.001			
328.00	329.50	D001188	1.50	0.006		0.006			
329.50	331.00	D001189	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			331.00	332.50	D001190	1.50		0.012		0.012
			332.50	334.00	D001191	1.50		0.007		0.007
			334.00	335.50	D001192	1.50		0.008		0.008
			335.50	337.00	D001193	1.50		0.010		0.010
			337.00	338.50	D001194	1.50		<0.005		0.001
			338.50	340.00	D001195	1.50		<0.005		0.001
			340.00	341.50	D001197	1.50		<0.005		0.001
			341.50	343.00	D001198	1.50		<0.005		0.001
			343.00	344.50	D001199	1.50		0.046		0.046
			344.50	346.00	D001200	1.50		<0.005		0.001
			346.00	347.50	D001201	1.50		<0.005		0.001
			347.50	349.00	D001202	1.50		<0.005		0.001
			349.00	350.30	D001203	1.30		<0.005		0.001
350.20	351.60	SY; FIN	350.30	351.60	D001204	1.30		0.017		0.017
		<b>Syénite 70°; Grains fins</b>	351.60	353.00	D001205	1.40		<0.005		0.001
		massive localement cisailé 40-60° ac, bréchique en fin d'éch,	353.00	354.50	D001207	1.50		<0.005		0.001
		veines de QZ, veinules et cheveux de carbonâtes, chloritisation	354.50	356.00	D001208	1.50		0.010		0.010
		et séricitisation	356.00	357.50	D001209	1.50		0.008		0.008
			357.50	359.00	D001210	1.50		0.108		0.108
			359.00	360.50	D001211	1.50		0.050		0.050
			360.50	362.00	D001212	1.50		0.060		0.060
362.00	364.00	SY; FIN	362.00	363.00	D001213	1.00		0.097		0.097
		<b>Syénite; Grains fins</b>	363.00	364.00	D001214	1.00		0.092		0.092
		qlq phénocristaux de FPautomorphe 0.2-1 cm localement	364.00	365.50	D001215	1.50		<0.005		0.001
		chloritisé et /ou epidotisé, K+, séricitisation, veinules et veines	365.50	367.00	D001217	1.50		0.016		0.016
		de QZ carbonaté, passage avec nodules chloritisés	367.00	368.50	D001218	1.50		0.029		0.029
			368.50	370.00	D001219	1.50		0.041		0.041
			370.00	371.50	D001220	1.50		0.008		0.008
			371.50	373.00	D001221	1.50		<0.005		0.001
			373.00	374.50	D001222	1.50		<0.005		0.001
			374.50	376.00	D001223	1.50		0.035		0.035
			376.00	377.50	D001224	1.50		0.217		0.217
			377.50	379.00	D001225	1.50		0.099		0.099

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
397.00      398.30      SY; FIN; RUB <b>Syénite; Grains fins; Rubané</b> légèrement cisailé et schisteuse, légèrement altéré en calcite, cisailé, altération en chlorite et séricite	379.00	380.50	D001227	1.50	0.019		0.019
	380.50	382.00	D001228	1.50	0.019		0.019
	382.00	383.50	D001229	1.50	0.126		0.126
	383.50	385.00	D001230	1.50	0.116		0.116
	385.00	386.50	D001231	1.50	0.038		0.038
	386.50	388.00	D001232	1.50	0.062		0.062
	388.00	389.50	D001233	1.50	<0.005		0.001
	389.50	391.00	D001234	1.50	<0.005		0.001
	391.00	392.50	D001235	1.50	<0.005		0.001
	392.50	394.00	D001237	1.50	<0.005		0.001
	394.00	395.50	D001238	1.50	<0.005		0.001
	395.50	397.00	D001239	1.50	<0.005		0.001
	397.00	398.30	D001240	1.30	0.116		0.116
	398.30	399.50	D001241	1.20	0.268		0.268
	399.50	401.00	D001242	1.50	0.194		0.194
	401.00	402.50	D001243	1.50	0.125		0.125
	402.50	404.00	D001244	1.50	0.165		0.165
	404.00	405.50	D001245	1.50	<0.005		0.001
	405.50	407.00	D001247	1.50	<0.005		0.001
	407.00	408.50	D001248	1.50	<0.005		0.001
	408.50	410.00	D001249	1.50	0.092		0.092
	410.00	411.50	D001250	1.50	0.907		0.907
	411.50	413.00	D001251	1.50	<0.005		0.001
	413.00	414.50	D001252	1.50	<0.005		0.001
	414.50	416.00	D001253	1.50	0.076		0.076
	416.00	417.50	D001254	1.50	<0.005		0.001
	417.50	419.00	D001255	1.50	<0.005		0.001
419.00	420.50	D001257	1.50	<0.005		0.001	
420.50	422.00	D001258	1.50	<0.005		0.001	
422.00	423.50	D001259	1.50	<0.005		0.001	
423.50	425.00	D001260	1.50	<0.005		0.001	
425.00	426.50	D001261	1.50	0.009		0.009	
426.50	428.00	D001262	1.50	<0.005		0.001	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			428.00	429.50	D001263	1.50	<0.005		0.001
			429.50	431.00	D001264	1.50	<0.005		0.001
			431.00	432.50	D001265	1.50	<0.005		0.001
			432.50	434.00	D001267	1.50	<0.005		0.001
			434.00	435.50	D001268	1.50	<0.005		0.001
			435.50	437.00	D001269	1.50	<0.005		0.001
			437.00	438.50	D001270	1.50	<0.005		0.001
438.50	442.60	SY; FIN; RUB	438.50	440.00	D001271	1.50	<0.005		0.001
		<b>Syénite; Grains fins; Rubané</b>	440.00	441.50	D001272	1.50	0.022		0.022
		cisaillé altéré en séricite et chlorite, avec localement K+++, cheveux 30-40° ac, BO++, K++ en debut et fin d'éch, PY irré dis	441.50	442.60	D001273	1.10	0.013		0.013
442.60	443.00	OM							
		<b>Ouverture minière</b>							
		defoncé							
443.00	443.90	SY; FIN; MAG	443.00	443.90	D001274	0.90	0.043		0.043
		<b>Syénite; Grains fins; Magnétique</b>							
		massive altération potassique, localement séricitisé, EP+							
443.90	445.00	OM							
		<b>Ouverture minière</b>							
445.00	449.80	SY; FIN	445.00	446.50	D001275	1.50	0.131		0.131
		<b>Syénite; Grains fins</b>	446.50	447.80	D001277	1.30	0.123		0.123
		massive altération potassique et séricitique	447.80	448.80	D001278	1.00	0.031		0.031
			448.80	449.80	D001279	1.00	0.635		0.635
449.80	451.80	OM							
		<b>Ouverture minière</b>							
451.80	454.60	SY; FIN	451.80	453.20	D001280	1.40	0.042		0.042
		<b>Syénite; Grains fins</b>	453.20	454.60	D001281	1.40	0.074		0.074
		altération potassique et séricitique, qlq phénocristaux							
454.60	Fin du sondage								
	Nombre d'échantillons : 311								
	Nombre d'échantillons QAQC : 34								
	Longueur totale échantillonnée : 449.20								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.00	14.50	D000946	D000945	1.50	<0.005	0.001
26.50	28.00	D000956	A3	1.50	0.555	0.555
40.00	41.50	D000966	D000965	1.50	0.123	0.123
53.50	55.00	D000976	M1	1.50	<0.005	0.001
66.50	68.00	D000986	D000985	1.50	0.049	0.049
80.00	81.50	D000996	B4	1.50	2.600	2.600
93.50	95.00	D001006	D001005	1.50	0.043	0.043
107.00	108.50	D001016	M1	1.50	<0.005	0.001
120.50	122.00	D001026	D001025	1.50	<0.005	0.001
133.50	135.00	D001036	C4	1.50	1.355	1.355
145.00	146.40	D001046	D001045	1.40	<0.005	0.001
157.00	158.40	D001056	M1	1.40	<0.005	0.001
170.50	172.00	D001066	D001065	1.50	<0.005	0.001
184.00	185.60	D001076	D2	1.60	0.827	0.827
196.50	198.00	D001086	D001085	1.50	0.154	0.154
209.40	210.40	D001096	M1	1.00	<0.005	0.001
222.50	224.00	D001106	D001105	1.50	0.005	0.005
235.00	236.50	D001116	F2	1.50	8.510	8.530
247.00	248.50	D001126	D001125	1.50	0.046	0.046
259.00	260.50	D001136	M1	1.50	<0.005	0.001
272.50	274.00	D001146	D001145	1.50	<0.005	0.001
286.00	287.50	D001156	G2	1.50	4.030	4.230
298.50	300.00	D001166	D001165	1.50	<0.005	0.001
311.50	313.00	D001176	M1	1.50	<0.005	0.001
325.00	326.50	D001186	D001185	1.50	<0.005	0.001
338.50	340.00	D001196	H	1.50	0.963	0.963
351.60	353.00	D001206	D001205	1.40	<0.005	0.001
364.00	365.50	D001216	M1	1.50	<0.005	0.001
377.50	379.00	D001226	D001225	1.50	0.084	0.084
391.00	392.50	D001236	A3	1.50	0.601	0.601
404.00	405.50	D001246	D001245	1.50	<0.005	0.001
417.50	419.00	D001256	M1	1.50	<0.005	0.001
431.00	432.50	D001266	D001265	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
445.00	446.50	D001276	B4	1.50	2.650	2.650



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-124**

Titre minier :

Section :                      630 100

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David Ruhara

Du :                      2010-03-05

Date de description :

Au :                     2010-03-08

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            137.00 m

Est	630 100.1
Nord	5 374 450.6
Élévation	284.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	1.60°	-63.10°	Oui
Reflex	5.00	1.60°	-63.10°	Oui
Reflex	8.00	1.60°	-63.00°	Oui
Reflex	11.00	1.60°	-62.90°	Oui
Reflex	14.00	1.80°	-62.90°	Oui
Reflex	17.00	8.60°	-62.30°	Oui
Reflex	20.00	332.70°	-61.40°	Oui
Reflex	23.00	347.80°	-60.20°	Oui
Reflex	26.00	356.80°	-59.10°	Oui
Reflex	29.00	353.20°	-58.70°	Oui
Reflex	32.00	347.80°	-58.10°	Oui
Reflex	35.00	234.40°	-58.40°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	332.80°	-59.20°	Oui
Reflex	41.00	358.00°	-59.10°	Non
Reflex	44.00	0.60°	-59.20°	Non
Reflex	47.00	1.10°	-59.10°	Non
Reflex	50.00	0.70°	-59.00°	Non
Reflex	53.00	359.10°	-59.00°	Non
Reflex	56.00	359.90°	-58.80°	Non
Reflex	59.00	0.30°	-58.80°	Non
Reflex	62.00	0.90°	-58.80°	Non
Reflex	65.00	359.50°	-58.80°	Non
Reflex	68.00	0.20°	-58.70°	Non
Reflex	71.00	359.20°	-58.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	360.00°	-58.80°	Non					
Reflex	77.00	0.90°	-58.60°	Non					
Reflex	80.00	2.20°	-58.50°	Non					
Reflex	83.00	2.10°	-58.80°	Non					
Reflex	86.00	2.00°	-58.60°	Non					
Reflex	89.00	1.90°	-58.50°	Non					
Reflex	92.00	358.50°	-58.80°	Non					
Reflex	95.00	2.00°	-58.60°	Non					
Reflex	98.00	1.40°	-58.50°	Non					
Reflex	101.00	0.70°	-58.80°	Non					
Reflex	104.00	1.20°	-58.50°	Non					
Reflex	107.00	0.90°	-58.70°	Non					
Reflex	110.00	1.00°	-58.80°	Non					
Reflex	113.00	1.00°	-58.50°	Non					
Reflex	116.00	0.30°	-58.70°	Non					
Reflex	119.00	0.70°	-58.60°	Non					
Reflex	122.00	1.30°	-58.60°	Non					
Reflex	125.00	0.10°	-58.60°	Non					
Reflex	128.00	0.80°	-58.60°	Non					
Reflex	131.00	1.10°	-58.30°	Non					
Reflex	134.00	0.70°	-58.40°	Non					
Reflex	137.00	1.30°	-58.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	32.00	MT <b>Mort-terrain</b>							
32.00	33.50	SY; FIN <b>Syénite; Grains fins</b> Massive à grains fins,microgrenue, porphyrique avec phénocristaux Xmm à rarement X cm,felsique, rougeâtre à qlq passage verdâtre,altéré différentiellement en CB, FK,MG,HM,CL,PY, SR, EP. Veine et veinule en CB et rarement en quartz, mm à cm.	32.00	33.50	D005853	1.50	0.008		0.008
33.50	35.00	NR <b>Carotte perdue</b>							
35.00	66.40	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique,phénocristaux Xmm à rarement Xcm, AK++, passage SR++.	35.00	36.50	D005854	1.50	0.024		0.024
			36.50	38.00	D005855	1.50	<0.005		0.001
			38.00	39.50	D005856	1.50	<0.005		0.001
			39.50	41.00	D005857	1.50	<0.005		0.001
			41.00	42.50	D005859	1.50	0.092		0.092
			42.50	44.00	D005860	1.50	0.137		0.137
			44.00	45.50	D005861	1.50	<0.005		0.001
			45.50	47.00	D005862	1.50	0.008		0.008
			47.00	48.70	D005864	1.70	<0.005		0.001
			48.70	50.00	D005865	1.30	<0.005		0.001
			50.00	51.50	D005866	1.50	<0.005		0.001
			51.50	53.00	D005867	1.50	0.079		0.079
			53.00	54.50	D005868	1.50	0.107		0.107
			54.50	56.00	D005869	1.50	0.019		0.019
			56.00	57.50	D005870	1.50	0.007		0.007
			57.50	59.00	D005871	1.50	0.247		0.247
			59.00	60.50	D005872	1.50	0.027		0.027
			60.50	62.00	D005874	1.50	0.016		0.016
			62.00	63.00	D005875	1.00	<0.005		0.001
			63.00	64.00	D005876	1.00	<0.005		0.001
			64.00	65.00	D005877	1.00	<0.005		0.001
			65.00	66.40	D005878	1.40	0.021		0.021
66.40	67.00	NR <b>Carotte perdue</b>							
67.00	121.00	SY; POR	67.00	68.50	D005879	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
<b>Syénite; Porphyrique</b>	68.50	70.00	D005880	1.50	0.005		0.005
Syénite porphyrique avec de phénocristaux Xmm à rarement Xcm sans orientation préférentielle.	70.00	71.50	D005881	1.50	<0.005		0.001
	71.50	73.00	D005882	1.50	<0.005		0.001
	73.00	74.50	D005884	1.50	<0.005		0.001
	74.50	76.00	D005885	1.50	0.007		0.007
	76.00	77.50	D005886	1.50	0.027		0.027
	77.50	79.00	D005887	1.50	0.077		0.077
	79.00	80.50	D005888	1.50	2.130		2.130
	80.50	82.00	D005889	1.50	0.964		0.964
	82.00	83.50	D005890	1.50	0.066		0.066
	83.50	85.00	D005891	1.50	0.191		0.191
	85.00	86.50	D005892	1.50	0.108		0.108
	86.50	88.00	D005894	1.50	0.040		0.040
	88.00	89.50	D005895	1.50	0.323		0.323
	89.50	91.00	D005896	1.50	0.531		0.531
	91.00	92.50	D005897	1.50	<0.005		0.001
	92.50	94.00	D005899	1.50	0.095		0.095
	94.00	95.50	D005900	1.50	0.021		0.021
	95.50	97.00	D005901	1.50	0.005		0.005
	97.00	98.50	D005902	1.50	<0.005		0.001
	98.50	100.00	D005904	1.50	<0.005		0.001
	100.00	101.50	D005905	1.50	0.060		0.060
	101.50	103.00	D005906	1.50	0.401		0.401
	103.00	104.50	D005907	1.50	0.099		0.099
	104.50	106.00	D005908	1.50	0.349		0.349
	106.00	107.50	D005909	1.50	0.006		0.006
	107.50	109.00	D005910	1.50	0.042		0.042
	109.00	110.50	D005911	1.50	0.106		0.106
	110.50	112.00	D005912	1.50	0.212		0.212
	112.00	113.50	D005914	1.50	0.131		0.131
	113.50	115.00	D005915	1.50	0.105		0.105
	115.00	116.50	D005916	1.50	0.314		0.314
	116.50	118.00	D005917	1.50	0.353		0.353

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
121.00	132.90	BA; AMY <b>Basalte; Amygdalaire</b> Basaltique, massive ,à grains fins, à moyennement cissaille avec rime. Amugydules à tendance allongé.	118.00	119.50	D005918	1.50	0.194		0.194
			119.50	121.00	D005919	1.50	0.566		0.566
			121.00	122.50	D005920	1.50	0.010		0.010
			122.50	124.00	D005921	1.50	<0.005		0.001
			124.00	125.50	D005922	1.50	<0.005		0.001
			125.50	127.00	D005924	1.50	0.005		0.005
			127.00	128.50	D005925	1.50	<0.005		0.001
			128.50	130.00	D005926	1.50	0.009		0.009
			130.00	131.50	D005927	1.50	0.005		0.005
			131.50	132.90	D005928	1.40	0.030		0.030
132.90	137.00	TU; GRO <b>Tuf à cendre/lapillis 35°; Grains grossiers</b> Tuf à cendre à grains moyens à grossiers, yeux de QZ.	132.90	134.00	D005929	1.10	0.843		0.843
			134.00	135.50	D005930	1.50	0.172		0.172
			135.50	137.00	D005931	1.50	0.112		0.112
137.00	Fin du sondage Nombre d'échantillons : 70 Nombre d'échantillons QAQC : 9 Longueur totale échantillonnée : 102.90								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
39.50	41.00	D005858	M1	1.50	<0.005	0.001
45.50	47.00	D005863	A3	1.50	0.479	0.479
59.00	60.50	D005873	D005872	1.50	0.147	0.147
71.50	73.00	D005883	D2	1.50	0.848	0.848
85.00	86.50	D005893	D005892	1.50	0.131	0.131
91.00	92.50	D005898	M1	1.50	<0.005	0.001
97.00	98.50	D005903	D2	1.50	0.846	0.846
110.50	112.00	D005913	D005912	1.50	0.208	0.208
124.00	125.50	D005923	B4	1.50	2.600	2.600

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-125**

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail :

Foré par :

Lot :

Décrit par :

Du :                    2010-03-11

Date de description :

Au :                    2010-03-12

Collet

UTM

Azimut :            0.00°  
 Plongée :           -60.00°  
 Longueur :        135.51 m

Est	630 000.0
Nord	5 374 449.2
Élévation	281.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	11.00	346.20°	-60.40°	Oui
Reflex	14.00	352.10°	-59.70°	Oui
Reflex	17.00	325.70°	-59.10°	Oui
Reflex	20.00	324.70°	-59.00°	Oui
Reflex	23.00	353.00°	-59.30°	Oui
Reflex	26.00	5.10°	-59.60°	Oui
Reflex	29.00	357.90°	-59.80°	Non
Reflex	32.00	359.40°	-59.80°	Non
Reflex	35.00	359.70°	-59.70°	Non
Reflex	38.00	359.10°	-59.70°	Non
Reflex	41.00	0.70°	-59.60°	Non
Reflex	44.00	359.40°	-59.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	47.00	359.90°	-59.50°	Non
Reflex	50.00	0.40°	-59.50°	Non
Reflex	53.00	0.60°	-59.40°	Non
Reflex	56.00	28.50°	-71.20°	Oui
Reflex	59.00	0.50°	-59.40°	Non
Reflex	62.00	0.40°	-59.40°	Non
Reflex	65.00	0.60°	-59.40°	Non
Reflex	68.00	0.70°	-59.40°	Non
Reflex	71.00	0.80°	-59.30°	Non
Reflex	74.00	0.70°	-59.30°	Non
Reflex	77.00	0.80°	-59.30°	Non
Reflex	80.00	0.90°	-59.20°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	83.00	1.00°	-59.30°	Non					
Reflex	86.00	1.10°	-59.20°	Non					
Reflex	89.00	1.20°	-59.20°	Non					
Reflex	92.00	1.20°	-59.20°	Non					
Reflex	95.00	1.30°	-59.20°	Non					
Reflex	98.00	1.40°	-59.30°	Non					
Reflex	101.00	1.30°	-59.20°	Non					
Reflex	104.00	1.30°	-59.20°	Non					
Reflex	107.00	1.30°	-59.10°	Non					
Reflex	110.00	1.40°	-59.10°	Non					
Reflex	113.00	1.40°	-59.00°	Non					
Reflex	116.00	1.40°	-59.10°	Non					
Reflex	119.00	1.40°	-59.20°	Non					
Reflex	122.00	1.40°	-59.10°	Non					
Reflex	125.00	1.30°	-59.10°	Non					
Reflex	128.00	1.40°	-59.00°	Non					
Reflex	131.00	1.40°	-59.00°	Non					
Reflex	134.00	1.30°	-58.90°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	26.80	MT <b>Mort-terrain</b> Mort-Terrain							
26.80	56.30	SY; POR <b>Syénite 45°; Porphyrique</b> Syénite porphyrique carbonatée, localement silicifiée, cisailé sur 80.0 cm au contact inf.	26.80	28.50	D010327	1.70	0.042	3.14	0.042
			28.50	30.00	D010328	1.50	0.027		0.027
			30.00	31.50	D010329	1.50	0.046		0.046
			31.50	33.00	D010330	1.50	0.145		0.145
			33.00	34.30	D010331	1.30	0.020		0.020
			34.30	36.00	D010332	1.70	0.201		0.201
			36.00	37.50	D010333	1.50	0.053		0.053
			37.50	39.00	D010334	1.50	0.055		0.055
			39.00	40.50	D010336	1.50	0.485		0.485
			40.50	42.00	D010337	1.50	0.262		0.262
			42.00	43.40	D010338	1.40	0.544		0.544
			43.40	45.00	D010339	1.60	0.486		0.486
			45.00	46.50	D010340	1.50	1.855		1.855
			46.50	48.00	D010341	1.50	0.894		0.894
			48.00	49.50	D010342	1.50	2.290		2.290
			49.50	51.10	D010343	1.60	0.807	0.807	
			51.10	52.80	D010344	1.70	1.025	1.025	
52.80	56.30	PO <b>Porphyre</b> Porphyre silicifié fortement carbonaté, cisailé et remplacé sur 80.0 cm au contact inf avec Bas	52.80	54.00	D010346	1.20	3.230	3.14	3.140
			54.00	55.00	D010347	1.00	1.760	1.760	
			55.00	56.30	D010348	1.30	2.270	2.270	
56.30	135.50	BA <b>Basalte</b> Basalte carbonaté avec localement, passages de volcanites felsiques.	56.30	58.00	D010349	1.70	0.011		0.011
			58.00	59.50	D010350	1.50	<0.005		0.001
			59.50	61.00	D010351	1.50	<0.005		0.001
			61.00	62.50	D010352	1.50	<0.005		0.001
			62.50	64.00	D010353	1.50	<0.005		0.001
			64.00	65.50	D010354	1.50	0.045		0.045
			65.50	67.00	D010356	1.50	<0.005		0.001
			67.00	68.50	D010357	1.50	<0.005		0.001
			68.50	69.50	D010358	1.00	0.010		0.010
			69.50	70.50	D010359	1.00	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
70.50	72.20	BRC <b>Brèche de coulée</b> Brèche de coulée felsique, possiblement une rhyolite avec fragment de porphyre syénitique, contac inf à 45° du CA.	70.50	72.20	D010360	1.70	2.680		2.680
			72.20	73.40	D010361	1.20	0.015		0.015
			73.40	74.20	D010362	0.80	0.207		0.207
			74.20	75.50	D010363	1.30	0.177		0.177
			75.50	77.00	D010364	1.50	0.006		0.006
			77.00	78.50	D010366	1.50	0.006		0.006
			78.50	80.00	D010367	1.50	<0.005		0.001
			80.00	81.50	D010368	1.50	0.027		0.027
			81.50	83.00	D010369	1.50	0.493		0.493
			83.00	84.50	D010370	1.50	<0.005		0.001
			84.50	86.00	D010371	1.50	<0.005		0.001
			86.00	87.50	D010372	1.50	0.007		0.007
			87.50	89.00	D010373	1.50	<0.005		0.001
			89.00	90.50	D010374	1.50	<0.005		0.001
			90.50	92.00	D010376	1.50	<0.005		0.001
			92.00	93.50	D010377	1.50	<0.005		0.001
			93.50	95.00	D010378	1.50	<0.005		0.001
			95.00	96.50	D010379	1.50	<0.005		0.001
			96.50	98.00	D010380	1.50	<0.005		0.001
			98.00	99.50	D010381	1.50	<0.005		0.001
99.50	101.00	D010382	1.50	<0.005		0.001			
101.00	102.50	D010383	1.50	<0.005		0.001			
102.50	104.00	D010384	1.50	<0.005		0.001			
104.00	105.50	D010386	1.50	<0.005		0.001			
105.50	107.00	D010387	1.50	0.014		0.014			
107.00	108.50	D010388	1.50	0.309		0.309			
108.50	110.00	D010389	1.50	<0.005		0.001			
110.00	111.50	D010390	1.50	<0.005		0.001			
111.50	113.00	D010391	1.50	<0.005		0.001			
113.00	114.50	D010392	1.50	<0.005		0.001			
114.50	116.00	D010393	1.50	<0.005		0.001			
116.00	117.50	D010394	1.50	<0.005		0.001			
117.50	119.00	D010396	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			119.00	120.50	D010397	1.50	<0.005		0.001
			120.50	122.00	D010398	1.50	<0.005		0.001
			122.00	123.50	D010399	1.50	0.013		0.013
			123.50	125.00	D010400	1.50	0.009		0.009
			125.00	126.50	D010401	1.50	0.506		0.506
			126.50	128.00	D010402	1.50	0.036		0.036
			128.00	129.50	D010403	1.50	<0.005		0.001
			129.50	131.00	D010404	1.50	<0.005		0.001
			131.00	132.50	D010406	1.50	0.062		0.062
			132.50	134.00	D010407	1.50	<0.005		0.001
			134.00	135.50	D010408	1.50	<0.005		0.001
135.50	135.51	OM Ouverture minière Open							
135.51	Fin du sondage Nombre d'échantillons : 74 Nombre d'échantillons QAQC : 8 Longueur totale échantillonnée : 108.70								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
37.50	39.00	D010335	D010334	1.50	0.053	0.053
51.10	52.80	D010345	F2	1.70	8.330	8.450
64.00	65.50	D010355	D010354	1.50	0.063	0.063
75.50	77.00	D010365	M1	1.50	<0.005	0.001
89.00	90.50	D010375	D010374	1.50	0.006	0.006
102.50	104.00	D010385	G2	1.50	4.060	4.000
116.00	117.50	D010395	D010394	1.50	<0.005	0.001
129.50	131.00	D010405	M1	1.50	<0.005	0.001

**Corporation Minière Osisko Div. Exploration**

**Sondage :**      **BD10-126**

Titre minier :

Section :                      630 000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :

Lot :

Décrit par :

Du :                      2010-03-09

Date de description :

Au :                      2010-03-11

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -45.00°  
 Longueur :                      125.00 m

Est	630 000.0
Nord	5 374 449.9
Élévation	281.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	295.40°	-44.50°	Oui
Reflex	5.00	351.40°	-44.50°	Oui
Reflex	8.00	9.90°	-44.70°	Oui
Reflex	11.00	344.70°	-45.00°	Oui
Reflex	14.00	328.80°	-45.10°	Oui
Reflex	17.00	325.80°	-44.90°	Oui
Reflex	20.00	26.70°	-44.70°	Oui
Reflex	23.00	352.30°	-44.60°	Oui
Reflex	26.00	345.00°	-44.20°	Oui
Reflex	29.00	357.10°	-43.80°	Oui
Reflex	32.00	343.90°	-44.00°	Oui
Reflex	35.00	351.10°	-44.00°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	98.40°	-44.10°	Oui
Reflex	41.00	0.30°	-44.00°	Oui
Reflex	44.00	1.70°	-44.00°	Non
Reflex	47.00	1.50°	-44.20°	Non
Reflex	50.00	1.90°	-44.10°	Non
Reflex	53.00	2.20°	-43.90°	Non
Reflex	56.00	2.10°	-43.80°	Non
Reflex	59.00	2.00°	-43.90°	Non
Reflex	62.00	2.10°	-43.50°	Non
Reflex	65.00	2.10°	-43.50°	Non
Reflex	68.00	2.00°	-43.40°	Non
Reflex	71.00	1.80°	-43.00°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.00°	-42.50°	Non					
Reflex	77.00	1.50°	-42.30°	Non					
Reflex	80.00	1.70°	-41.80°	Non					
Reflex	83.00	1.50°	-41.70°	Non					
Reflex	86.00	1.60°	-41.40°	Non					
Reflex	89.00	1.20°	-41.20°	Non					
Reflex	92.00	1.20°	-41.00°	Non					
Reflex	95.00	1.40°	-40.70°	Non					
Reflex	98.00	1.10°	-40.70°	Non					
Reflex	101.00	1.40°	-40.70°	Non					
Reflex	104.00	1.20°	-40.90°	Non					
Reflex	107.00	1.30°	-40.70°	Non					
Reflex	110.00	1.40°	-40.60°	Non					
Reflex	113.00	1.10°	-40.80°	Non					
Reflex	116.00	1.40°	-40.50°	Non					
Reflex	119.00	1.50°	-40.60°	Non					
Reflex	122.00	1.40°	-40.40°	Non					
Reflex	125.00	1.40°	-40.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	40.30	MT <b>Mort-terrain</b>						
40.30	45.40	SY <b>Syénite 45°</b> Syénite carbonaté et séricitisé, localement cisailé.	40.30	42.00	D010409	1.70	1.805	1.805
			42.00	43.00	D010410	1.00	1.855	1.855
			43.00	44.00	D010411	1.00	2.450	2.450
			44.00	45.40	D010412	1.40	1.225	1.225
45.40	97.60	BA <b>Basalte</b> Basalte carbonaté avec passage de niveaux andésitiques.	45.40	47.00	D010413	1.60	0.025	0.025
			47.00	48.50	D010414	1.50	0.047	0.047
			48.50	50.00	D010416	1.50	0.057	0.057
			50.00	51.50	D010417	1.50	0.006	0.006
			51.50	53.00	D010418	1.50	0.009	0.009
			53.00	54.40	D010419	1.40	<0.005	0.001
54.30	56.00	BA; BRC <b>Basalte 60°; Brèche de coulée</b> Brèche de volcanite mafique localement silicifié.	54.40	56.00	D010420	1.60	0.138	0.138
			56.00	57.30	D010421	1.30	0.013	0.013
			57.30	59.00	D010422	1.70	0.013	0.013
			59.00	60.50	D010423	1.50	<0.005	0.001
			60.50	62.00	D010424	1.50	0.056	0.056
			62.00	63.50	D010426	1.50	<0.005	0.001
			63.50	65.00	D010427	1.50	<0.005	0.001
			65.00	66.50	D010428	1.50	<0.005	0.001
			66.50	68.00	D010429	1.50	<0.005	0.001
			68.00	69.50	D010430	1.50	<0.005	0.001
			69.50	71.00	D010431	1.50	0.008	0.008
			71.00	72.50	D010432	1.50	<0.005	0.001
			72.50	74.00	D010433	1.50	<0.005	0.001
			74.00	75.50	D010434	1.50	<0.005	0.001
			75.50	77.00	D010436	1.50	<0.005	0.001
			77.00	78.50	D010437	1.50	0.006	0.006
			78.50	80.00	D010438	1.50	<0.005	0.001
			80.00	81.50	D010439	1.50	<0.005	0.001
			81.50	83.00	D010440	1.50	<0.005	0.001
			83.00	84.00	D010441	1.00	<0.005	0.001
			84.00	85.30	D010442	1.30	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
97.60	103.30	RY; BRC <b>Rhyolite 35°; Brèche de coulée</b> Brèche de coulée rhyolitique gris-foncé avec injections de qtz blanc démembrées, contact inf avec bas à 40° du CA.	85.30	86.90	D010443	1.60	0.120	3.19	0.120
			86.90	88.50	D010444	1.60	2.390		2.390
			88.50	90.00	D010446	1.50	0.041		0.041
			90.00	91.50	D010447	1.50	0.859		0.859
			91.50	93.00	D010448	1.50	0.211		0.211
			93.00	94.50	D010449	1.50	0.034		0.034
			94.50	95.70	D010450	1.20	0.019		0.019
			95.70	96.70	D010451	1.00	0.005		0.005
			96.70	98.00	D010452	1.30	3.130		3.190
			98.00	99.50	D010453	1.50	3.270		3.720
			99.50	101.00	D010454	1.50	4.440		4.310
			101.00	102.00	D010456	1.00	3.630		3.740
			103.30	125.00	BA <b>Basalte</b> Basalte localement amygdulaire carbonaté.	102.00	103.00		D010457
103.00	104.30	D010458				1.30	1.145	1.145	
104.30	106.00	D010459				1.70	0.069	0.069	
106.00	107.50	D010460				1.50	0.007	0.007	
107.50	109.00	D010461				1.50	0.024	0.024	
109.00	110.50	D010462				1.50	<0.005	0.001	
110.50	112.00	D010463				1.50	0.005	0.005	
112.00	113.50	D010464				1.50	0.005	0.005	
113.50	115.00	D010466				1.50	0.005	0.005	
115.00	116.50	D010467				1.50	0.005	0.005	
116.50	118.00	D010468				1.50	<0.005	0.001	
118.00	119.50	D010469				1.50	<0.005	0.001	
119.50	121.00	D010470				1.50	0.005	0.005	
121.00	122.50	D010471	1.50	<0.005	0.001				
122.50	124.00	D010472	1.50	<0.005	0.001				
124.00	125.00	D010473	1.00	<0.005	0.001				
125.00	Fin du sondage Nombre d'échantillons : 59 Nombre d'échantillons QAQC : 6 Longueur totale échantillonnée : 84.70								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
47.00	48.50	D010415	D010414	1.50	0.028	0.028
60.50	62.00	D010425	H	1.50	1.030	1.030
74.00	75.50	D010435	D010434	1.50	<0.005	0.001
86.90	88.50	D010445	A3	1.60	0.591	0.591
99.50	101.00	D010455	D010454	1.50	5.210	5.350
112.00	113.50	D010465	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-127**

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail :

Foré par :      Bradley

Lot :

Décrit par :      David Ruhara

Du :

Date de description :

Au :

Collet

Azimut :            0.00°  
 Plongée :           -60.00°  
 Longueur :        193.71 m

UTM

Est	630 500.1
Nord	5 374 500.1
Élévation	299.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	5.10°	-60.30°	Non
Reflex	5.00	358.50°	-60.30°	Oui
Reflex	8.00	5.50°	-60.30°	Non
Reflex	11.00	5.50°	-60.30°	Non
Reflex	14.00	6.60°	-60.30°	Non
Reflex	17.00	5.60°	-60.30°	Non
Reflex	20.00	5.80°	-60.40°	Non
Reflex	23.00	10.40°	-60.40°	Oui
Reflex	26.00	6.00°	-60.40°	Non
Reflex	29.00	6.80°	-60.40°	Non
Reflex	32.00	6.30°	-60.40°	Non
Reflex	35.00	7.20°	-60.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	4.30°	-60.40°	Non
Reflex	41.00	3.20°	-60.40°	Non
Reflex	44.00	2.90°	-60.50°	Non
Reflex	47.00	5.30°	-60.40°	Non
Reflex	50.00	6.40°	-60.40°	Non
Reflex	53.00	5.30°	-60.50°	Non
Reflex	56.00	4.40°	-60.40°	Non
Reflex	59.00	3.80°	-60.40°	Non
Reflex	62.00	5.60°	-60.40°	Non
Reflex	65.00	5.10°	-60.40°	Non
Reflex	68.00	3.70°	-60.50°	Non
Reflex	71.00	4.30°	-60.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	5.30°	-60.40°	Non	Reflex	173.00	6.10°	-60.30°	Non
Reflex	77.00	4.60°	-60.40°	Non	Reflex	176.00	6.40°	-60.30°	Non
Reflex	80.00	4.40°	-60.40°	Non	Reflex	179.00	5.50°	-60.30°	Non
Reflex	83.00	4.10°	-60.40°	Non	Reflex	182.00	5.30°	-60.30°	Non
Reflex	86.00	4.00°	-60.40°	Non	Reflex	185.00	4.00°	-61.40°	Non
Reflex	89.00	4.40°	-60.40°	Non	Reflex	188.00	4.40°	-59.60°	Non
Reflex	92.00	5.00°	-60.40°	Non	Reflex	191.00	5.10°	-59.80°	Non
Reflex	95.00	5.60°	-60.40°	Non					
Reflex	98.00	4.20°	-60.40°	Non					
Reflex	101.00	3.90°	-60.40°	Non					
Reflex	104.00	3.30°	-60.40°	Non					
Reflex	107.00	2.90°	-60.30°	Non					
Reflex	110.00	3.00°	-60.40°	Non					
Reflex	113.00	2.70°	-60.30°	Non					
Reflex	116.00	4.40°	-60.40°	Non					
Reflex	119.00	7.30°	-60.40°	Non					
Reflex	122.00	7.40°	-60.40°	Non					
Reflex	125.00	5.70°	-60.40°	Oui					
Reflex	128.00	7.80°	-60.40°	Non					
Reflex	131.00	7.30°	-60.30°	Non					
Reflex	134.00	5.80°	-60.30°	Non					
Reflex	137.00	3.50°	-60.30°	Non					
Reflex	140.00	5.90°	-60.30°	Non					
Reflex	143.00	5.70°	-60.30°	Non					
Reflex	146.00	4.90°	-60.30°	Non					
Reflex	149.00	5.00°	-60.30°	Non					
Reflex	152.00	6.30°	-60.30°	Oui					
Reflex	155.00	4.60°	-60.30°	Non					
Reflex	158.00	4.60°	-60.30°	Non					
Reflex	161.00	4.80°	-60.30°	Non					
Reflex	164.00	5.30°	-60.30°	Non					
Reflex	167.00	5.00°	-60.30°	Non					
Reflex	170.00	6.00°	-60.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT						
		<b>Mort-terrain</b>						
2.20	182.00	SY; POR	2.20	3.50	D005243	1.30	<0.005	0.001
		<b>Syénite; Porphyrique</b>	3.50	5.00	D005244	1.50	<0.005	0.001
		Syénite porphyrique avec de phénocristaux à tendance équi-granulaire	5.00	6.50	D005245	1.50	<0.005	0.001
		, blanchâtre à rosé, Xmm à rarement Xcm et faiblement magnétisé.	6.50	8.00	D005246	1.50	<0.005	0.001
			8.00	9.50	D005247	1.50	<0.005	0.001
			9.50	11.00	D005248	1.50	<0.005	0.001
			11.00	12.50	D005249	1.50	<0.005	0.001
			12.50	14.00	D005250	1.50	<0.005	0.001
			14.00	15.50	D005251	1.50	<0.005	0.001
			15.50	17.00	D005253	1.50	<0.005	0.001
			17.00	18.50	D005254	1.50	<0.005	0.001
			18.50	20.00	D005255	1.50	<0.005	0.001
			20.00	21.50	D005256	1.50	<0.005	0.001
			21.50	23.00	D005258	1.50	<0.005	0.001
			23.00	24.50	D005259	1.50	<0.005	0.001
			24.50	26.00	D005260	1.50	<0.005	0.001
			26.00	27.50	D005261	1.50	<0.005	0.001
			27.50	29.00	D005263	1.50	<0.005	0.001
			29.00	30.50	D005264	1.50	<0.005	0.001
			30.50	32.00	D005265	1.50	<0.005	0.001
			32.00	33.50	D005266	1.50	<0.005	0.001
			33.50	35.00	D005267	1.50	<0.005	0.001
			35.00	36.50	D005268	1.50	<0.005	0.001
			36.50	38.00	D005269	1.50	<0.005	0.001
			38.00	39.50	D005270	1.50	0.299	0.299
			39.50	41.00	D005271	1.50	0.005	0.005
			41.00	42.50	D005273	1.50	<0.005	0.001
			42.50	44.00	D005274	1.50	<0.005	0.001
			44.00	45.50	D005275	1.50	<0.005	0.001
			45.50	47.00	D005276	1.50	<0.005	0.001
			47.00	48.50	D005277	1.50	<0.005	0.001
			48.50	50.00	D005278	1.50	0.007	0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.50	D005279	1.50	0.007		0.007
	51.50	53.00	D005280	1.50	0.035		0.035
	53.00	54.50	D005281	1.50	0.029		0.029
	54.50	56.00	D005283	1.50	0.078		0.078
	56.00	57.50	D005284	1.50	<0.005		0.001
	57.50	59.00	D005285	1.50	0.123		0.123
	59.00	60.50	D005286	1.50	<0.005		0.001
	60.50	62.00	D005287	1.50	0.138		0.138
	62.00	63.50	D005288	1.50	<0.005		0.001
	63.50	65.00	D005289	1.50	<0.005		0.001
	65.00	66.50	D005290	1.50	<0.005		0.001
	66.50	68.00	D005291	1.50	0.008		0.008
	68.00	69.50	D005293	1.50	0.005		0.005
	69.50	71.00	D005294	1.50	0.014		0.014
	71.00	72.50	D005295	1.50	<0.005		0.001
	72.50	74.00	D005296	1.50	0.033		0.033
	74.00	75.50	D005298	1.50	0.005		0.005
	75.50	77.00	D005299	1.50	<0.005		0.001
	77.00	78.50	D005300	1.50	0.009		0.009
	78.50	80.00	D005301	1.50	<0.005		0.001
	80.00	81.00	D005302	1.00	<0.005		0.001
	81.00	82.30	D005303	1.30	<0.005		0.001
	82.30	83.50	D005304	1.20	<0.005		0.001
	83.50	85.00	D005305	1.50	<0.005		0.001
	85.00	86.50	D005306	1.50	0.061		0.061
	86.50	88.00	D005308	1.50	0.006		0.006
	88.00	89.50	D005309	1.50	<0.005		0.001
	89.50	91.00	D005310	1.50	0.013		0.013
	91.00	92.50	D005311	1.50	<0.005		0.001
	92.50	94.00	D005312	1.50	<0.005		0.001
	94.00	95.50	D005313	1.50	0.009		0.009
	95.50	97.00	D005314	1.50	0.077		0.077
	97.00	98.50	D005315	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.50	100.00	D005316	1.50	0.113		0.113
	100.00	101.50	D005318	1.50	<0.005		0.001
	101.50	103.00	D005319	1.50	<0.005		0.001
	103.00	104.50	D005320	1.50	0.239		0.239
	104.50	106.00	D005321	1.50	0.160		0.160
	106.00	107.50	D005322	1.50	0.035		0.035
	107.50	109.00	D005323	1.50	0.025		0.025
	109.00	110.50	D005324	1.50	0.025		0.025
	110.50	112.00	D005325	1.50	0.008		0.008
	112.00	113.50	D005326	1.50	0.018		0.018
	113.50	115.00	D005328	1.50	<0.005		0.001
	115.00	116.50	D005329	1.50	0.005		0.005
	116.50	118.00	D005330	1.50	<0.005		0.001
	118.00	119.50	D005331	1.50	<0.005		0.001
	119.50	121.00	D005332	1.50	<0.005		0.001
	121.00	122.50	D005333	1.50	<0.005		0.001
	122.50	124.00	D005334	1.50	<0.005		0.001
	124.00	125.50	D005335	1.50	0.019		0.019
	125.50	127.00	D005336	1.50	<0.005		0.001
	127.00	128.50	D005338	1.50	<0.005		0.001
	128.50	130.00	D005339	1.50	0.005		0.005
	130.00	131.50	D005340	1.50	<0.005		0.001
	131.50	133.00	D005341	1.50	<0.005		0.001
	133.00	134.50	D005343	1.50	0.012		0.012
	134.50	136.00	D005344	1.50	0.005		0.005
	136.00	137.50	D005345	1.50	0.007		0.007
	137.50	139.00	D005346	1.50	<0.005		0.001
	139.00	140.50	D005348	1.50	<0.005		0.001
	140.50	142.00	D005349	1.50	0.020		0.020
	142.00	143.50	D005350	1.50	0.030		0.030
	143.50	145.00	D005351	1.50	0.012		0.012
	145.00	146.50	D005352	1.50	0.043		0.043
	146.50	148.00	D005353	1.50	0.022		0.022

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			148.00	149.50	D005354	1.50		0.021	0.021
			149.50	151.00	D005355	1.50		<0.005	0.001
			151.00	152.50	D005356	1.50		<0.005	0.001
			152.50	154.00	D005358	1.50		0.011	0.011
			154.00	155.50	D005359	1.50		<0.005	0.001
			155.50	157.00	D005360	1.50		0.007	0.007
			157.00	158.50	D005361	1.50		<0.005	0.001
			158.50	160.00	D005362	1.50		<0.005	0.001
			160.00	161.50	D005363	1.50		<0.005	0.001
			161.50	163.00	D005364	1.50		<0.005	0.001
			163.00	164.50	D005365	1.50		<0.005	0.001
			164.50	166.00	D005366	1.50		<0.005	0.001
			166.00	167.50	D005368	1.50		<0.005	0.001
			167.50	169.00	D005369	1.50		0.008	0.008
			169.00	170.50	D005370	1.50		0.007	0.007
			170.50	172.00	D005371	1.50		0.023	0.023
			172.00	173.50	D005372	1.50		0.009	0.009
			173.50	175.00	D005373	1.50		0.020	0.020
			175.00	176.50	D005374	1.50		0.014	0.014
			176.50	178.00	D005375	1.50		0.049	0.049
			178.00	179.50	D005376	1.50		0.031	0.031
			179.50	181.00	D005378	1.50		0.008	0.008
			181.00	182.00	D005379	1.00		<0.005	0.001
182.00	185.00	OM <b>Ouverture minière</b> Ouverture mière.							
185.00	193.70	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, grains fins, porhyrique avec de phénocristaux Xmm .	185.00	186.50	D005380	1.50		0.017	0.017
			186.50	188.00	D005381	1.50		0.009	0.009
			188.00	189.50	D005383	1.50		<0.005	0.001
			189.50	191.00	D005384	1.50		<0.005	0.001
			191.00	192.50	D005385	1.50		0.007	0.007
			192.50	193.70	D005386	1.20		0.015	0.015
193.70	193.71	OM <b>Ouverture minière</b>							

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Ouverture minière.							
<p>193.71      Fin du sondage                      Nombre d'échantillons : 127                      Nombre d'échantillons QAQC : 18                      Longueur totale échantillonnée : 188.50</p>							



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
2.20	3.50	D005242	B4	1.30	2.540	2.540
14.00	15.50	D005252	D005251	1.50	<0.005	0.001
20.00	21.50	D005257	M1	1.50	<0.005	0.001
26.00	27.50	D005262	H2	1.50	0.979	0.979
39.50	41.00	D005272	D005271	1.50	0.009	0.009
53.00	54.50	D005282	D2	1.50	0.864	0.864
66.50	68.00	D005292	D005291	1.50	<0.005	0.001
72.50	74.00	D005297	M1	1.50	<0.005	0.001
85.00	86.50	D005307	A3	1.50	0.595	0.595
98.50	100.00	D005317	D005316	1.50	0.186	0.186
112.00	113.50	D005327	H2	1.50	0.969	0.969
125.50	127.00	D005337	D005336	1.50	<0.005	0.001
131.50	133.00	D005342	M1	1.50	<0.005	0.001
137.50	139.00	D005347	D2	1.50	0.844	0.844
151.00	152.50	D005357	D005356	1.50	<0.005	0.001
164.50	166.00	D005367	B4	1.50	2.620	2.620
178.00	179.50	D005377	D005376	1.50	0.020	0.020
186.50	188.00	D005382	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-128**

Titre minier :

Section :                      631 300

Canton :

Niveau :

Rang :

Place de travail :

Foré par :

Lot :

Décrit par :

Du :                      2010-03-07

Date de description :

Au :                      2010-03-08

Collet

UTM

Azimut :                      180.00°

Plongée :                      -60.00°

Longueur :                      146.00 m

Est                      631 300.0

Nord                      5 374 349.8

Élévation                      299.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	14.00	353.00°	-59.40°	Oui
Reflex	17.00	345.10°	-57.90°	Oui
Reflex	20.00	173.00°	-59.40°	Oui
Reflex	23.00	177.20°	-59.30°	Oui
Reflex	26.00	180.40°	-59.20°	Non
Reflex	29.00	180.60°	-59.10°	Non
Reflex	32.00	180.00°	-58.90°	Non
Reflex	35.00	180.50°	-58.70°	Non
Reflex	38.00	180.50°	-59.00°	Non
Reflex	41.00	179.90°	-58.90°	Non
Reflex	44.00	180.00°	-59.00°	Non
Reflex	47.00	179.40°	-58.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	50.00	180.40°	-58.80°	Non
Reflex	53.00	180.80°	-58.60°	Non
Reflex	56.00	179.60°	-58.60°	Non
Reflex	59.00	178.80°	-58.40°	Non
Reflex	62.00	178.60°	-58.30°	Non
Reflex	65.00	179.60°	-58.40°	Non
Reflex	68.00	179.90°	-58.40°	Non
Reflex	71.00	180.30°	-58.20°	Non
Reflex	74.00	180.40°	-58.10°	Non
Reflex	77.00	181.10°	-58.10°	Non
Reflex	80.00	181.80°	-58.00°	Non
Reflex	83.00	180.60°	-57.90°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	86.00	181.30°	-57.80°	Non					
Reflex	89.00	179.70°	-57.70°	Non					
Reflex	92.00	180.00°	-57.60°	Non					
Reflex	95.00	181.20°	-57.50°	Non					
Reflex	98.00	184.00°	-57.60°	Oui					
Reflex	101.00	181.50°	-57.50°	Non					
Reflex	104.00	181.50°	-57.40°	Non					
Reflex	107.00	181.70°	-57.20°	Non					
Reflex	110.00	181.90°	-57.20°	Non					
Reflex	113.00	181.80°	-57.00°	Non					
Reflex	116.00	181.60°	-56.90°	Non					
Reflex	119.00	181.70°	-56.90°	Non					
Reflex	122.00	181.50°	-56.70°	Non					
Reflex	125.00	181.50°	-56.60°	Non					
Reflex	128.00	180.30°	-56.50°	Non					
Reflex	131.00	181.60°	-56.30°	Non					
Reflex	134.00	175.40°	-56.10°	Oui					
Reflex	137.00	181.60°	-56.00°	Non					
Reflex	140.00	181.70°	-56.00°	Non					
Reflex	143.00	181.80°	-55.90°	Non					
Reflex	146.00	181.90°	-55.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	11.00	MT <b>Mort-terrain</b>						
11.00	29.70	BA <b>Basalte</b> Volcanique basalte andésitique avec les grains fins à moyens, amugdalair.	11.00	12.50	D005136	1.50	<0.005	0.001
			12.50	14.00	D005138	1.50	<0.005	0.001
			14.00	15.50	D005139	1.50	<0.005	0.001
			15.50	16.60	D005140	1.10	<0.005	0.001
			16.60	18.00	D005141	1.40	<0.005	0.001
			18.00	19.00	D005143	1.00	<0.005	0.001
			19.00	20.10	D005144	1.10	<0.005	0.001
			20.10	21.60	D005145	1.50	<0.005	0.001
21.60	22.70	DI; GRO <b>Diorite; Grains grossiers</b> Dyke intermediaire à composition dioritique à grains grossiers.	21.60	22.70	D005146	1.10	<0.005	0.001
			22.70	24.00	D005147	1.30	<0.005	0.001
			24.00	25.50	D005148	1.50	<0.005	0.001
			25.50	27.00	D005149	1.50	<0.005	0.001
			27.00	28.50	D005150	1.50	<0.005	0.001
			28.50	29.70	D005151	1.20	<0.005	0.001
29.70	37.00	SY; POR <b>Syénite 45°; Porphyrique</b> Syénite porphyrique avec phénocristaux Xmm à tendance équigranulaire.	29.70	31.00	D005153	1.30	<0.005	0.001
			31.00	32.50	D005154	1.50	<0.005	0.001
			32.50	34.00	D005155	1.50	<0.005	0.001
			34.00	35.50	D005156	1.50	<0.005	0.001
			35.50	37.00	D005157	1.50	<0.005	0.001
37.00	87.50	BA; AMY <b>Basalte 35°; Amygdalaire</b> Basalte à grains fins avec de amugdules, qqq veines de CB.	37.00	38.50	D005158	1.50	<0.005	0.001
			38.50	40.00	D005159	1.50	<0.005	0.001
			40.00	41.50	D005160	1.50	<0.005	0.001
			41.50	43.00	D005161	1.50	<0.005	0.001
			43.00	44.50	D005163	1.50	<0.005	0.001
			44.50	46.00	D005164	1.50	<0.005	0.001
			46.00	47.50	D005165	1.50	<0.005	0.001
			47.50	49.00	D005166	1.50	<0.005	0.001
			49.00	50.50	D005167	1.50	<0.005	0.001
			50.50	52.00	D005168	1.50	<0.005	0.001
			52.00	53.50	D005169	1.50	<0.005	0.001
			53.50	55.00	D005170	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			55.00	56.50	D005171	1.50	<0.005		0.001
			56.50	58.00	D005173	1.50	<0.005		0.001
			58.00	59.50	D005174	1.50	0.056		0.056
			59.50	61.00	D005175	1.50	<0.005		0.001
			61.00	62.50	D005176	1.50	<0.005		0.001
			62.50	64.00	D005178	1.50	<0.005		0.001
			64.00	65.50	D005179	1.50	0.008		0.008
			65.50	67.00	D005180	1.50	0.015		0.015
			67.00	68.50	D005181	1.50	0.012		0.012
			68.50	70.00	D005183	1.50	0.008		0.008
			70.00	71.50	D005184	1.50	<0.005		0.001
			71.50	73.00	D005185	1.50	0.008		0.008
			73.00	74.50	D005186	1.50	<0.005		0.001
			74.50	76.00	D005187	1.50	0.006		0.006
			76.00	77.50	D005188	1.50	0.006		0.006
			77.50	79.00	D005189	1.50	0.310		0.310
			79.00	80.50	D005190	1.50	0.974		0.974
			80.50	82.00	D005191	1.50	0.086		0.086
			82.00	83.20	D005193	1.20	0.007		0.007
			83.20	84.50	D005194	1.30	0.006		0.006
			84.50	86.00	D005195	1.50	<0.005		0.001
			86.00	87.50	D005196	1.50	<0.005		0.001
87.50	92.00	TU; FIN; MTY	87.50	89.00	D005197	1.50	<0.005		0.001
		<b>Tuf à cendre/lapillis 35°; Grains fins; Grains moyens</b>	89.00	90.50	D005198	1.50	0.005		0.005
		Tuf à cendre et lapillis avec de fragments Xmm à Xcm.	90.50	92.00	D005199	1.50	0.009		0.009
92.00	146.00	BA; AMY	92.00	93.50	D005200	1.50	<0.005		0.001
		<b>Basalte; Amygdalaire</b>	93.50	95.00	D005201	1.50	<0.005		0.001
		Basalte à grains fins avec des amygdules. Qlq VCB.	95.00	96.50	D005203	1.50	<0.005		0.001
			96.50	98.00	D005204	1.50	<0.005		0.001
			98.00	99.50	D005205	1.50	<0.005		0.001
			99.50	101.00	D005206	1.50	0.171		0.171
			101.00	102.50	D005207	1.50	<0.005		0.001
			102.50	104.00	D005208	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	104.00	105.50	D005209	1.50	<0.005		0.001
	105.50	107.00	D005210	1.50	<0.005		0.001
	107.00	108.50	D005211	1.50	<0.005		0.001
	108.50	110.00	D005213	1.50	<0.005		0.001
	110.00	111.50	D005214	1.50	<0.005		0.001
	111.50	113.00	D005215	1.50	0.009		0.009
	113.00	114.50	D005216	1.50	<0.005		0.001
	114.50	116.00	D005218	1.50	0.006		0.006
	116.00	117.50	D005219	1.50	<0.005		0.001
	117.50	119.00	D005220	1.50	0.008		0.008
	119.00	120.50	D005221	1.50	0.005		0.005
	120.50	122.00	D005223	1.50	0.008		0.008
	122.00	123.50	D005224	1.50	<0.005		0.001
	123.50	125.00	D005225	1.50	<0.005		0.001
	125.00	126.50	D005226	1.50	<0.005		0.001
	126.50	128.00	D005227	1.50	<0.005		0.001
	128.00	129.50	D005228	1.50	<0.005		0.001
	129.50	131.00	D005229	1.50	0.006		0.006
	131.00	132.50	D005230	1.50	<0.005		0.001
	132.50	134.00	D005231	1.50	0.010		0.010
	134.00	135.50	D005233	1.50	0.005		0.005
	135.50	137.00	D005234	1.50	0.006		0.006
	137.00	138.50	D005235	1.50	0.006		0.006
	138.50	140.00	D005236	1.50	<0.005		0.001
	140.00	140.80	D005237	0.80	<0.005		0.001
140.80	142.30	SY; POR	D005238	1.50	0.013		0.013
		<b>Syénite 55°; Porphyrique</b>	D005239	1.20	<0.005		0.001
		Dyke à composition syénitique porphyrique.	D005240	1.50	<0.005		0.001
			D005241	1.00	0.006		0.006
146.00	<b>Fin du sondage</b> Nombre d'échantillons : 93 Nombre d'échantillons QAQC : 13 Longueur totale échantillonnée : 135.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
11.00	12.50	D005137	M1	1.50	<0.005	0.001
16.60	18.00	D005142	D2	1.40	0.595	0.595
28.50	29.70	D005152	D005151	1.20	<0.005	0.001
41.50	43.00	D005162	F2	1.50	8.240	8.440
55.00	56.50	D005172	D005171	1.50	<0.005	0.001
61.00	62.50	D005177	M1	1.50	0.006	0.006
67.00	68.50	D005182	G2	1.50	3.470	4.100
80.50	82.00	D005192	D005191	1.50	0.087	0.087
93.50	95.00	D005202	H	1.50	0.961	0.961
107.00	108.50	D005212	D005211	1.50	<0.005	0.001
113.00	114.50	D005217	M1	1.50	<0.005	0.001
119.00	120.50	D005222	A3	1.50	0.596	0.596
132.50	134.00	D005232	D005231	1.50	0.007	0.007

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-129**

Titre minier :

Section :                      631300

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          D. Tremblay

Du :                      2010-03-08

Date de description :

Au :                     2010-03-13

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            497.00 m

Est	631 300.1
Nord	5 374 300.1
Élévation	301.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	14.00	335.10°	-60.40°	Oui
Reflex	17.00	335.00°	-60.30°	Oui
Reflex	20.00	335.10°	-60.40°	Oui
Reflex	23.00	0.70°	-60.60°	Non
Reflex	26.00	0.40°	-59.90°	Non
Reflex	29.00	2.10°	-59.80°	Oui
Reflex	32.00	0.80°	-60.20°	Non
Reflex	35.00	0.40°	-57.40°	Non
Reflex	38.00	357.70°	-59.60°	Oui
Reflex	41.00	0.90°	-58.80°	Non
Reflex	44.00	359.20°	-58.90°	Non
Reflex	47.00	0.90°	-58.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	50.00	1.70°	-58.40°	Non
Reflex	53.00	2.40°	-58.10°	Non
Reflex	56.00	3.00°	-57.80°	Non
Reflex	59.00	1.80°	-57.30°	Non
Reflex	62.00	1.00°	-56.90°	Non
Reflex	65.00	2.00°	-56.70°	Non
Reflex	68.00	2.60°	-56.50°	Non
Reflex	71.00	2.20°	-56.20°	Non
Reflex	74.00	0.80°	-55.20°	Non
Reflex	77.00	1.00°	-55.80°	Non
Reflex	80.00	1.10°	-56.00°	Non
Reflex	83.00	0.90°	-55.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	86.00	1.10°	-55.70°	Non	Reflex	185.00	1.20°	-54.80°	Non
Reflex	89.00	0.90°	-55.70°	Non	Reflex	188.00	1.40°	-54.80°	Non
Reflex	92.00	3.50°	-58.30°	Oui	Reflex	191.00	1.40°	-54.80°	Non
Reflex	95.00	1.00°	-55.60°	Non	Reflex	194.00	1.80°	-54.80°	Non
Reflex	98.00	1.30°	-55.70°	Non	Reflex	197.00	2.80°	-54.80°	Non
Reflex	101.00	1.50°	-55.20°	Non	Reflex	200.00	1.00°	-54.80°	Non
Reflex	104.00	1.20°	-55.60°	Non	Reflex	203.00	1.20°	-54.70°	Non
Reflex	107.00	0.80°	-55.50°	Non	Reflex	206.00	0.90°	-54.70°	Non
Reflex	110.00	1.40°	-55.40°	Non	Reflex	209.00	0.90°	-54.60°	Non
Reflex	113.00	1.20°	-55.40°	Non	Reflex	212.00	1.20°	-54.50°	Non
Reflex	116.00	1.40°	-55.40°	Non	Reflex	215.00	1.00°	-54.30°	Non
Reflex	119.00	1.40°	-55.40°	Non	Reflex	218.00	1.70°	-54.40°	Non
Reflex	122.00	1.20°	-55.20°	Non	Reflex	221.00	2.30°	-54.30°	Non
Reflex	125.00	1.40°	-55.10°	Non	Reflex	224.00	1.40°	-54.40°	Non
Reflex	128.00	1.40°	-55.10°	Non	Reflex	227.00	2.10°	-54.30°	Non
Reflex	131.00	1.50°	-55.10°	Non	Reflex	230.00	2.00°	-54.30°	Non
Reflex	134.00	1.30°	-55.10°	Non	Reflex	233.00	358.70°	-54.30°	Oui
Reflex	137.00	1.10°	-55.00°	Non	Reflex	236.00	1.80°	-54.30°	Non
Reflex	140.00	0.80°	-55.00°	Non	Reflex	239.00	2.00°	-54.30°	Non
Reflex	143.00	1.90°	-54.90°	Non	Reflex	242.00	2.00°	-54.20°	Non
Reflex	146.00	2.00°	-54.90°	Non	Reflex	245.00	0.90°	-54.10°	Oui
Reflex	149.00	3.10°	-55.00°	Non	Reflex	248.00	1.80°	-54.10°	Non
Reflex	152.00	3.80°	-54.90°	Non	Reflex	251.00	1.10°	-54.10°	Non
Reflex	155.00	2.70°	-55.00°	Non	Reflex	254.00	1.20°	-54.20°	Non
Reflex	158.00	1.20°	-55.00°	Non	Reflex	257.00	1.30°	-54.20°	Non
Reflex	161.00	3.30°	-55.00°	Non	Reflex	260.00	1.50°	-54.20°	Non
Reflex	164.00	0.50°	-54.90°	Oui	Reflex	263.00	1.80°	-54.10°	Non
Reflex	167.00	2.60°	-54.90°	Non	Reflex	266.00	3.60°	-54.20°	Non
Reflex	170.00	2.10°	-55.00°	Non	Reflex	269.00	4.60°	-54.00°	Non
Reflex	173.00	359.00°	-55.10°	Non	Reflex	272.00	4.10°	-53.90°	Non
Reflex	176.00	1.00°	-54.90°	Non	Reflex	275.00	4.60°	-53.90°	Non
Reflex	179.00	1.20°	-54.90°	Non	Reflex	278.00	2.80°	-53.80°	Oui
Reflex	182.00	1.00°	-54.90°	Non	Reflex	281.00	4.20°	-53.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	284.00	3.30°	-53.70°	Non
Reflex	287.00	3.40°	-53.70°	Non
Reflex	290.00	1.90°	-53.60°	Non
Reflex	293.00	2.70°	-53.40°	Non
Reflex	296.00	4.00°	-53.40°	Non
Reflex	299.00	1.90°	-53.20°	Non
Reflex	302.00	1.30°	-53.20°	Non
Reflex	305.00	1.30°	-53.20°	Non
Reflex	308.00	3.20°	-53.20°	Non
Reflex	311.00	5.40°	-53.20°	Oui
Reflex	314.00	2.70°	-53.20°	Non
Reflex	317.00	3.70°	-53.20°	Non
Reflex	320.00	1.60°	-53.10°	Non
Reflex	323.00	3.20°	-53.20°	Non
Reflex	326.00	2.50°	-53.20°	Non
Reflex	329.00	3.00°	-53.20°	Non
Reflex	332.00	3.70°	-53.20°	Non
Reflex	335.00	3.00°	-53.20°	Non
Reflex	338.00	4.40°	-53.20°	Non
Reflex	341.00	3.60°	-53.20°	Non
Reflex	344.00	3.10°	-53.10°	Non
Reflex	347.00	5.40°	-53.20°	Oui
Reflex	350.00	2.30°	-53.10°	Non
Reflex	353.00	2.40°	-53.10°	Non
Reflex	356.00	1.90°	-53.10°	Non
Reflex	359.00	2.90°	-53.10°	Non
Reflex	362.00	2.90°	-53.10°	Non
Reflex	365.00	4.00°	-53.10°	Non
Reflex	368.00	4.50°	-53.10°	Non
Reflex	371.00	2.60°	-53.10°	Non
Reflex	374.00	4.00°	-53.00°	Non
Reflex	377.00	4.10°	-53.00°	Non
Reflex	380.00	2.80°	-53.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	383.00	0.50°	-53.10°	Oui
Reflex	386.00	3.80°	-53.10°	Non
Reflex	389.00	3.70°	-53.10°	Non
Reflex	392.00	1.80°	-53.10°	Non
Reflex	395.00	2.40°	-53.10°	Non
Reflex	398.00	4.30°	-53.10°	Oui
Reflex	401.00	2.80°	-53.20°	Non
Reflex	404.00	2.70°	-53.20°	Non
Reflex	407.00	3.40°	-53.20°	Non
Reflex	410.00	3.40°	-53.40°	Non
Reflex	413.00	2.50°	-53.20°	Non
Reflex	416.00	2.40°	-53.20°	Non
Reflex	419.00	2.50°	-53.10°	Non
Reflex	422.00	2.60°	-53.00°	Non
Reflex	425.00	4.40°	-53.10°	Non
Reflex	428.00	359.20°	-53.00°	Oui
Reflex	431.00	6.70°	-53.00°	Non
Reflex	434.00	4.80°	-52.90°	Non
Reflex	437.00	4.60°	-53.00°	Non
Reflex	440.00	3.20°	-53.00°	Non
Reflex	443.00	1.60°	-53.10°	Non
Reflex	446.00	1.90°	-53.00°	Non
Reflex	449.00	3.00°	-53.10°	Non
Reflex	452.00	5.50°	-53.10°	Non
Reflex	455.00	3.80°	-53.10°	Non
Reflex	458.00	6.00°	-53.00°	Non
Reflex	461.00	5.60°	-53.10°	Non
Reflex	464.00	5.00°	-53.10°	Non
Reflex	467.00	1.20°	-53.10°	Non
Reflex	470.00	3.70°	-53.00°	Non
Reflex	473.00	5.90°	-53.00°	Non
Reflex	476.00	4.40°	-53.00°	Non
Reflex	479.00	4.40°	-53.00°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	482.00	5.30°	-53.10°	Non					
Reflex	485.00	3.50°	-53.00°	Oui					
Reflex	488.00	4.40°	-53.00°	Non					
Reflex	491.00	4.20°	-53.00°	Non					
Reflex	494.00	2.90°	-53.00°	Non					
Reflex	497.00	3.00°	-53.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.55	MT						
		<b>Mort-terrain</b>						
5.55	60.17	BA	5.55	7.00	D015001	1.45	<0.005	0.001
		<b>Basalte</b>						
		Basalte vert foncé, à grains fins, équigranulaire, massif. Il est dur, silicifié et carbonatisé.	7.00	8.00	D015003	1.00	<0.005	0.001
		Il est magnétique. Nous observons de rares amygdules, remplies de carbonates.	8.00	9.50	D015004	1.50	<0.005	0.001
		Présence de plusieurs fractures occupées par des veinules de carbonates, disposées surtout entre 0°-20°ac et ne dépassant 1cm en épaisseur.	9.50	11.00	D015005	1.50	<0.005	0.001
		Nous observons une brèche de coulée entre 27.05-27.70 mètres.	11.00	12.50	D015006	1.50	<0.005	0.001
		À partir de la cote de 56.36 mètres, le basalte est silicifié, dur et de teinte gris foncé, grisâtre et beige. Nous observons aussi des amygdules. Il est peut-être coussiné.	12.50	14.00	D015007	1.50	<0.005	0.001
			14.00	15.50	D015008	1.50	<0.005	0.001
			15.50	17.00	D015009	1.50	<0.005	0.001
			17.00	18.50	D015010	1.50	<0.005	0.001
			18.50	20.00	D015011	1.50	<0.005	0.001
			20.00	21.50	D015013	1.50	<0.005	0.001
			21.50	23.00	D015014	1.50	<0.005	0.001
			23.00	24.50	D015015	1.50	<0.005	0.001
			24.50	26.00	D015016	1.50	<0.005	0.001
			26.00	27.50	D015017	1.50	<0.005	0.001
			27.50	29.00	D015018	1.50	<0.005	0.001
			29.00	30.50	D015019	1.50	<0.005	0.001
29.50	30.10	FAI	30.50	32.00	D015020	1.50	<0.005	0.001
		<b>Faille</b>	32.00	33.50	D015021	1.50	<0.005	0.001
		Zone de faille accompagnée de brèche. Nous observons des fragments sub-angulaires dans une matrice chloriteuse.	33.50	35.00	D015023	1.50	<0.005	0.001
		La récupération de la carotte est mauvaise.	35.00	36.50	D015024	1.50	<0.005	0.001
			36.50	38.00	D015025	1.50	<0.005	0.001
			38.00	39.50	D015026	1.50	0.028	0.028
			39.50	41.00	D015027	1.50	0.395	0.395
			41.00	42.50	D015028	1.50	<0.005	0.001
			42.50	44.00	D015029	1.50	<0.005	0.001
			44.00	45.50	D015030	1.50	<0.005	0.001
			45.50	47.00	D015031	1.50	<0.005	0.001
			47.00	48.50	D015033	1.50	<0.005	0.001
			48.50	50.00	D015034	1.50	<0.005	0.001
			50.00	51.50	D015035	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
60.17	497.00	<p>SY; POR</p> <p><b>Syénite 45°; Porphyrique</b></p> <p>Syénite porphyrique massive, altérée, de teinte très variée, dure et assez homogène en composition.</p> <p>Sa couleur varie de grisâtre, gris foncé, beige, vert pâle et surtout rougeâtre et rosée. Les zones non altérées sont pas fréquentes et la couleur est gris foncé, verdâtre.</p> <p>Elle se compose entre 10-30% de feldspaths porphyriques, surtout hypi à idiomorphes et pouvant atteindre jusqu'à 1x1cm en dimensions. Il est fréquent d'observer de la zonation des porphyres. Certains se présentent sous forme de lattes (2-3mmx1cm). La matrice est aphanitique, feldspathique.</p> <p>Cet intrusif est fortement fracturé, avec injection de matériel albite-carbonates et parfois tapissées de chlorite.</p> <p>Nous observons des enclaves de roches volcaniques (basalte altéré).</p> <p>Par endroits, cet intrusif est injecté d'un système de veinules de quartz-albite.</p> <p>Faiblement magnétique par endroits.</p>	51.50	53.00	D015036	1.50	<0.005		0.001
			53.00	54.50	D015037	1.50	<0.005		0.001
			54.50	56.00	D015038	1.50	<0.005		0.001
			56.00	57.50	D015039	1.50	<0.005		0.001
			57.50	59.00	D015041	1.50	<0.005		0.001
			59.00	60.17	D015043	1.17	0.047		0.047
			60.17	61.00	D015044	0.83	0.020		0.020
61.00	61.65	<p>BA</p> <p><b>Basalte</b></p> <p>Enclave de basalte altéré.</p>	61.00	62.00	D015045	1.00	0.005		0.005
			62.00	63.50	D015046	1.50	0.006		0.006
			63.50	65.00	D015047	1.50	<0.005		0.001
			65.00	66.50	D015048	1.50	0.006		0.006
			66.50	68.00	D015049	1.50	0.017		0.017
			68.00	69.50	D015050	1.50	0.027		0.027
			69.50	71.00	D015051	1.50	0.008		0.008
			71.00	72.50	D015053	1.50	0.063		0.063
			72.50	74.00	D015054	1.50	0.732		0.732
			74.00	75.50	D015055	1.50	0.005		0.005
			75.50	77.00	D015056	1.50	0.157		0.157
			77.00	78.50	D015057	1.50	0.011		0.011
78.50	80.00	D015058	1.50	0.085		0.085			

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			80.00	81.50	D015059	1.50		0.189		0.189
			81.50	83.00	D015060	1.50		0.085		0.085
			83.00	84.50	D015061	1.50		0.064		0.064
			84.50	86.00	D015063	1.50		<0.005		0.001
			86.00	87.50	D015064	1.50		0.026		0.026
			87.50	89.00	D015065	1.50		0.025		0.025
			89.00	90.50	D015066	1.50		<0.005		0.001
			90.50	92.00	D015067	1.50		<0.005		0.001
			92.00	93.50	D015068	1.50		0.005		0.005
			93.50	95.00	D015069	1.50		<0.005		0.001
			95.00	96.50	D015070	1.50		<0.005		0.001
			96.50	98.00	D015071	1.50		0.331		0.331
			98.00	99.50	D015073	1.50		0.199		0.199
			99.50	101.00	D015074	1.50		0.472		0.472
			101.00	102.50	D015075	1.50		0.696		0.696
			102.50	104.00	D015076	1.50		0.674		0.674
			104.00	105.50	D015077	1.50		0.082		0.082
			105.50	107.00	D015078	1.50		0.081		0.081
			107.00	108.50	D015079	1.50		0.128		0.128
108.50	110.90	CIS	108.50	110.00	D015081	1.50		0.368		0.368
		<b>Cisaillage 70°</b>	110.00	110.90	D015083	0.90		0.071		0.071
		Syénite cisailée, altérée, vert pâle, gris violacée, et gris foncé parfois.	110.90	112.00	D015084	1.10		0.057		0.057
		Elle se présente à grains fins surtout et porphyrique par endroits. Nous observons des grains de chlorite allongés selon une schistosité à 70°ac.	112.00	113.00	D015085	1.00		0.086		0.086
		La quantité de porphyres ne dépassent 10-12% .	113.00	114.50	D015086	1.50		0.107		0.107
		Les contacts sont assez francs.	114.50	116.00	D015087	1.50		0.459		0.459
		Pyrite fine disséminée et concentrée selon des fractures.	116.00	117.50	D015088	1.50		2.210		2.210
			117.50	119.00	D015089	1.50		1.015		1.015
			119.00	120.50	D015090	1.50		0.786		0.786
			120.50	122.00	D015091	1.50		0.575		0.575
			122.00	123.50	D015093	1.50		0.841		0.841
			123.50	125.00	D015094	1.50		1.870		1.870
			125.00	126.00	D015095	1.00		1.770		1.770
			126.00	127.40	D015096	1.40		2.090		2.090

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
127.39	129.90	CIS	127.40	128.50	D015097	1.10	0.700		0.700
		<b>Cisaillement 60°</b>	128.50	129.90	D015098	1.40	0.066		0.066
		Syénite cisailée. Idem à l'horizon observé entre 108.50-110.9 mètres. Sa teinte est vert pâle	129.90	131.00	D015099	1.10	0.009		0.009
		Nous observons des porphyres de feldspaths et des grains de chlorite, allongés.	131.00	132.50	D015100	1.50	<0.005		0.001
		C'est peut-être la syénite altérée, déformée.	132.50	134.00	D015101	1.50	<0.005		0.001
		Le passage à 129.90 est très graduel.	134.00	135.50	D015103	1.50	0.006		0.006
		Schistosité à 60°ac	135.50	137.00	D015104	1.50	<0.005		0.001
			137.00	138.50	D015105	1.50	0.027		0.027
			138.50	140.00	D015106	1.50	0.083		0.083
			140.00	141.50	D015107	1.50	0.006		0.006
			141.50	143.00	D015108	1.50	0.032		0.032
			143.00	144.50	D015109	1.50	0.014		0.014
			144.50	146.00	D015110	1.50	<0.005		0.001
			146.00	147.50	D015111	1.50	<0.005		0.001
			147.50	149.00	D015113	1.50	0.005		0.005
			149.00	150.50	D015114	1.50	0.020		0.020
			150.50	152.00	D015115	1.50	0.005		0.005
			152.00	153.50	D015116	1.50	0.005		0.005
			153.50	155.00	D015117	1.50	0.124		0.124
			155.00	156.50	D015118	1.50	0.028		0.028
			156.50	158.00	D015119	1.50	0.293		0.293
			158.00	159.50	D015121	1.50	<0.005		0.001
			159.50	161.00	D015123	1.50	0.005		0.005
			161.00	162.50	D015124	1.50	0.127		0.127
			162.50	164.00	D015125	1.50	0.005		0.005
			164.00	165.50	D015126	1.50	0.321		0.321
			165.50	167.00	D015127	1.50	0.560		0.560
			167.00	168.50	D015128	1.50	0.254		0.254
			168.50	170.00	D015129	1.50	0.141		0.141
			170.00	171.50	D015130	1.50	0.025		0.025
			171.50	173.00	D015131	1.50	0.021		0.021
			173.00	174.50	D015133	1.50	0.044		0.044
			174.50	176.00	D015134	1.50	1.445		1.445

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			176.00	177.50	D015135	1.50		0.359		0.359
			177.50	179.00	D015136	1.50		0.509		0.509
			179.00	180.50	D015137	1.50		0.521		0.521
			180.50	182.00	D015138	1.50		0.051		0.051
			182.00	183.50	D015139	1.50		0.035		0.035
			183.50	185.00	D015140	1.50		<0.005		0.001
			185.00	186.50	D015141	1.50		0.108		0.108
			186.50	188.00	D015143	1.50		0.030		0.030
187.60	187.80	FAI	188.00	189.50	D015144	1.50		0.008		0.008
		<b>Faille</b>	189.50	191.00	D015145	1.50		0.029		0.029
		Zone de faille.	191.00	192.50	D015146	1.50		1.115		1.115
		Nous observons des fragments angulaires de syénite hématisée dans une matrice de chlorite.	192.50	194.00	D015147	1.50		1.235		1.235
		La récupération est passable.								
192.65	193.00	CIS	194.00	195.50	D015148	1.50		0.063		0.063
		<b>Cisaillement 60°</b>	195.50	197.00	D015149	1.50		<0.005		0.001
		Cisaillement d'intensité moyenne.								
		Son épaisseur est de 22cm.								
197.00	199.86	CIS	197.00	198.50	D015150	1.50		<0.005		0.001
		<b>Cisaillement 65°</b>	198.50	200.00	D015151	1.50		<0.005		0.001
		Syénite cisailée de teinte vert pâle.	200.00	201.50	D015153	1.50		<0.005		0.001
		Son inrtensité est moyenne.	201.50	203.00	D015154	1.50		<0.005		0.001
		Elle est carbonatisée et séricitisée pare endroits.	203.00	204.50	D015155	1.50		<0.005		0.001
			204.50	206.00	D015156	1.50		<0.005		0.001
			206.00	207.50	D015157	1.50		<0.005		0.001
			207.50	209.00	D015158	1.50		0.018		0.018
			209.00	210.50	D015159	1.50		0.010		0.010
			210.50	212.00	D015161	1.50		<0.005		0.001
			212.00	213.50	D015163	1.50		<0.005		0.001
			213.50	215.00	D015164	1.50		<0.005		0.001
			215.00	216.50	D015165	1.50		<0.005		0.001
			216.50	218.00	D015166	1.50		<0.005		0.001
			218.00	219.50	D015167	1.50		0.020		0.020
			219.50	221.00	D015168	1.50		<0.005		0.001
			221.00	222.50	D015169	1.50		0.126		0.126



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
229.32	229.51	<p>CIS</p> <p><b>Cisaillement 35°</b></p> <p>Cisaillement d'intensité moyenne et ayant 10cm en épaisseur. Il est carbonatisé. Présence d'une veinule de quartz, concordante à la déformation.</p>	222.50	224.00	D015170	1.50	<0.005		0.001
			224.00	225.50	D015171	1.50	<0.005		0.001
			225.50	227.00	D015173	1.50	<0.005		0.001
			227.00	228.50	D015174	1.50	<0.005		0.001
			228.50	230.00	D015175	1.50	<0.005		0.001
			230.00	231.50	D015176	1.50	<0.005		0.001
			231.50	233.00	D015177	1.50	<0.005		0.001
			233.00	234.50	D015178	1.50	0.733		0.733
			234.50	236.00	D015179	1.50	2.640		2.640
			236.00	237.50	D015180	1.50	0.037		0.037
			237.50	239.00	D015181	1.50	0.037		0.037
			239.00	240.50	D015183	1.50	0.005		0.005
			240.50	242.00	D015184	1.50	0.020		0.020
			242.00	243.50	D015185	1.50	<0.005		0.001
			243.50	245.00	D015186	1.50	0.005		0.005
			245.00	246.50	D015187	1.50	0.036		0.036
			246.50	248.00	D015188	1.50	0.011		0.011
248.00	249.50	D015189	1.50	0.012		0.012			
249.50	251.00	D015190	1.50	<0.005		0.001			
251.00	252.50	D015191	1.50	<0.005		0.001			
252.50	254.00	D015193	1.50	<0.005		0.001			
253.95	256.98	<p>CIS</p> <p><b>Cisaillement 25°</b></p> <p>Syénite cisailée, altérée et injectée par un système de veinules et veines de quartz-carbonates-chlorite et tourmaline parfois. Sa teinte est vert pâle. La schistosité est bien développée et disposée entre 0°-20°ac et accompagnée de plissement par endroits. Nous observons des taches grossières de chlorite, allongées selon la déformation. Présence de feuillets fins de séricite. Le système veiné est disposé surtout entre 25°-70°ac et variant de 1-30cm en épaisseur et parfois selon l'ac. La tourmaline se présente amorphe. Les carbonates sont rosés parfois. Le système veiné représente environ 35% du volume de la carotte. Présence de veinules d'albite-quartz, déformées et sectionnées.</p>	254.00	255.50	D015194	1.50	0.037		0.037
			255.50	257.00	D015195	1.50	0.045		0.045
			257.00	258.50	D015196	1.50	<0.005		0.001
			258.50	260.00	D015197	1.50	<0.005		0.001
			260.00	261.50	D015198	1.50	<0.005		0.001
			261.50	263.00	D015199	1.50	<0.005		0.001
			263.00	264.50	D015201	1.50	<0.005		0.001
			264.50	266.00	D015203	1.50	<0.005		0.001
			266.00	267.50	D015204	1.50	<0.005		0.001
			267.50	269.00	D015205	1.50	<0.005		0.001
269.00	270.50	D015206	1.50	<0.005		0.001			
270.50	272.00	D015207	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Traces de pyrite en cubes moyens.				272.00	273.30	D015208	1.30	0.022		0.022
				273.30	274.50	D015209	1.20	0.091		0.091
				274.50	276.00	D015210	1.50	0.165		0.165
				276.00	277.00	D015211	1.00	0.015		0.015
				277.00	278.00	D015213	1.00	0.074		0.074
				278.00	279.50	D015214	1.50	1.955		1.955
				279.50	281.00	D015215	1.50	0.760		0.760
				281.00	282.50	D015216	1.50	0.005		0.005
				282.50	284.00	D015217	1.50	<0.005		0.001
				284.00	285.50	D015218	1.50	<0.005		0.001
				285.50	287.00	D015219	1.50	0.011		0.011
				287.00	288.50	D015220	1.50	0.242		0.242
				287.10	287.30	CIS	288.50	290.00	D015221	1.50
<b>Cisaillement 35°</b> Petit cisaillement ayant environ 8cm en épaisseur. Son intensité est moyenne. Il est carbonatisé, séricité.				290.00	291.50	D015223	1.50	<0.005		0.001
				291.50	293.00	D015224	1.50	<0.005		0.001
				293.00	294.50	D015225	1.50	<0.005		0.001
				294.50	296.00	D015226	1.50	<0.005		0.001
				296.00	297.50	D015227	1.50	<0.005		0.001
295.82	295.92	CIS	297.50	299.00	D015228	1.50	<0.005		0.001	
<b>Cisaillement 50°</b> Petit cisaillement ayant environ 5cm en épaisseur. Il est carbonatisé et chloritisé.				299.00	300.50	D015229	1.50	<0.005		0.001
				300.50	302.00	D015230	1.50	<0.005		0.001
				302.00	303.50	D015231	1.50	0.009		0.009
				303.50	305.00	D015233	1.50	0.009		0.009
				305.00	306.10	D015234	1.10	0.007		0.007
				306.10	307.20	D015235	1.10	0.109		0.109
				307.20	308.10	FAI	307.20	308.60	D015236	1.40
<b>Faïlle 15°</b> Zone de faille: fragments angulaires de syénite dans une matrice de chlorite et d'un peu de quartz.				308.60	310.00	D015237	1.40	0.039		0.039
				310.00	311.00	D015238	1.00	0.175		0.175
310.70	311.54	IF	311.00	312.50	D015239	1.50	0.569		0.569	
<b>Intrusion felsique 55°</b> Dyke de syénite porphyrique. Les porphyres de felkspaths se présentent essentiellement sous forme de lattes, ne dépassant 0.5x1cm en dimensions. Les contacts sont assez nets, évidents.				312.50	314.00	D015241	1.50	0.090		0.090
				314.00	315.50	D015243	1.50	0.083		0.083
				315.50	317.00	D015244	1.50	0.125		0.125
				317.00	318.50	D015245	1.50	0.353		0.353

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			318.50	320.00	D015246	1.50	<0.005		0.001
			320.00	321.50	D015247	1.50	<0.005		0.001
			321.50	323.00	D015248	1.50	<0.005		0.001
			323.00	324.50	D015249	1.50	0.018		0.018
			324.50	326.00	D015250	1.50	0.006		0.006
			326.00	327.50	D015251	1.50	<0.005		0.001
			327.50	329.00	D015253	1.50	<0.005		0.001
			329.00	330.50	D015254	1.50	<0.005		0.001
			330.50	332.00	D015255	1.50	<0.005		0.001
			332.00	333.50	D015256	1.50	0.062		0.062
			333.50	334.50	D015257	1.00	0.225		0.225
			334.50	335.50	D015258	1.00	0.059		0.059
334.54	336.50	FAI	335.50	336.50	D015259	1.00	0.147		0.147
		<b>Faïlle 20°</b>	336.50	338.00	D015260	1.50	0.093		0.093
		Zone de brèche et de faille, injectée par du matériel pegmatitique rosâtre et un système de veinules de quartz-chlorite, gris foncé, gris blanc.	338.00	339.50	D015261	1.50	0.032		0.032
		La faille proprement dite se retrouve entre 335.8-336.1 mètres et est disposée à 15°ac. Nous observons des fragments sub-angulaires à sub-arrondis de syénite dans une matrice de chlorite.	339.50	340.40	D015263	0.90	0.050		0.050
340.40	342.50	QZVN	340.40	341.90	D015264	1.50	1.440		1.440
		<b>Veine de Quartz massive 20°</b>	341.90	343.00	D015266	1.10	0.595		0.595
		Veine de quartz- chlorite-carbonates, gris foncé, gris blanc très fracturée et minéralisée en pyrite-spécularite et nous etOR VISIBLE.							
		Les fractures sont occupées par de la chlorite et par de la spécularite.							
		La pyrite (2-3%) se présente en cubes fins à moyens surtout présente dans les éponges.							
		À la cote de 341.6 m, nous observons 4-5 points d'OR VISIBLE fin.							
		Les carbonates possèdent une teinte rosée.							
		À partir de 340.4 mètres, les porphyres de feldspaths sont rares, altérés.							
343.00	344.16	QZVN	343.00	344.00	D015267	1.00	1.500		1.500
		<b>Veine de Quartz massive 15°</b>	344.00	345.00	D015268	1.00	0.969		0.969
		Veine de quartz-chlorite-carbonates, gris blanc, très fracturée.							

Corporation Minière Osisko Div. Exploration

Description		Analyse							
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
346.72	347.42	<p>Les fracturures sont tapissées de chlorite et séricite parfois. Les carbonates sont rosés parfois.</p> <p>Pyrite (tr-1%) surtout présente dans les épontes, en cubes fins à moyens.</p> <p><b>QZVN</b></p> <p><b>Veine de Quartz massive 25°</b></p> <p>Nous observons un ensemble de veinules et veines de quartz-carbonates, gris blanc, disposées entre 20°-30°ac et parfois selon l'ac.</p> <p>Elles varient de 0.5-5cm en épaisseur.</p> <p>Pyrite (2-3%) en cubes fins à moyens et surtout présente dans les épontes.</p>	345.00	346.00	D015269	1.00	0.008		0.008
			346.00	347.00	D015270	1.00	1.390		1.390
			347.00	348.50	D015271	1.50	0.724		0.724
			348.50	350.00	D015273	1.50	0.063		0.063
			350.00	351.00	D015274	1.00	0.051		0.051
			351.00	352.00	D015275	1.00	0.053		0.053
			352.00	353.00	D015276	1.00	0.195		0.195
352.60	352.97	<p>FAI</p> <p><b>Faille 20°</b></p> <p>Excellente faille disposée à 20°ac et ayant 9cm en épaisseur.</p> <p>Nous observons en grande majorité des fragments très angulaires de veines de quartz dans une matrice de chlorite.</p> <p>Présence d'effraiments de syénite.</p> <p>Les épontes sont bréchiques.</p>							
352.97	353.40	<p>CIS</p> <p><b>Cisaillement 40°</b></p> <p>Cisaillement d'intensité moyenne et ayant une épaisseur de 40cm. Il est recoupé par l'extension de la faille.</p> <p>Il est séricitisé.</p>	353.00	354.00	D015277	1.00	0.068		0.068
			354.00	355.00	D015278	1.00	0.097		0.097
			355.00	356.00	D015279	1.00	<0.005		0.001
			356.00	357.50	D015281	1.50	<0.005		0.001
			357.50	359.00	D015283	1.50	0.060		0.060
			359.00	360.50	D015284	1.50	0.021		0.021
			360.50	362.00	D015285	1.50	0.050		0.050
			362.00	363.50	D015286	1.50	0.069		0.069
			363.50	365.00	D015287	1.50	0.077		0.077
			365.00	366.50	D015288	1.50	0.510		0.510
			366.50	368.00	D015289	1.50	0.089		0.089
			368.00	369.50	D015290	1.50	0.023		0.023
			369.50	371.00	D015291	1.50	0.009		0.009
			371.00	372.50	D015293	1.50	0.016		0.016
372.50	374.00	D015294	1.50	0.380		0.380			
374.00	375.50	D015295	1.50	0.040		0.040			
375.50	377.00	D015296	1.50	<0.005		0.001			
377.00	378.50	D015297	1.50	0.866		0.866			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
384.38	384.75	CIS <b>Cisaillement 50°</b> Cisaillement d'intensité faible. Il est carbonaté.	378.50	380.00	D015298	1.50	0.074		0.074
			380.00	381.50	D015299	1.50	0.045		0.045
			381.50	383.00	D015300	1.50	0.134		0.134
			383.00	384.50	D015301	1.50	0.021		0.021
			384.50	386.00	D015303	1.50	0.394		0.394
			386.00	387.50	D015304	1.50	0.109		0.109
			387.50	389.00	D015305	1.50	0.030		0.030
			389.00	390.50	D015306	1.50	0.080		0.080
			390.50	392.00	D015307	1.50	0.160		0.160
			392.00	393.50	D015308	1.50	0.015		0.015
			393.50	395.00	D015309	1.50	0.007		0.007
			395.00	396.50	D015310	1.50	<0.005		0.001
			396.50	398.00	D015311	1.50	<0.005		0.001
			398.00	399.50	D015313	1.50	<0.005		0.001
			399.50	401.00	D015314	1.50	0.025		0.025
			401.00	402.50	D015315	1.50	<0.005		0.001
			402.50	404.00	D015316	1.50	<0.005		0.001
			404.00	405.50	D015317	1.50	0.005		0.005
			405.50	407.00	D015318	1.50	<0.005		0.001
407.00	408.50	D015319	1.50	0.978		0.978			
408.80	411.50	CIS <b>Cisaillement 55°</b> Cisaillement d'intensité faible à moyenne, chloritisé, carbonaté et hématisé par endroits. Sa teinte est vert pâle surtout et rosé parfois. Injecté par quelques veinules et veines de quartz-carbonates roses et chlorite concordantes à la déformation. Nous observons un système de quartz-carbonates-feldspaths, du type pegmatitique, recoupant la schistosité.	408.50	410.00	D015321	1.50	0.084		0.084
			410.00	411.50	D015323	1.50	0.006		0.006
			411.50	413.00	D015324	1.50	<0.005		0.001
			413.00	414.50	D015325	1.50	0.024		0.024
			414.50	416.00	D015326	1.50	0.011		0.011
			416.00	417.50	D015327	1.50	<0.005		0.001
			417.50	419.00	D015328	1.50	<0.005		0.001
			419.00	420.50	D015329	1.50	<0.005		0.001
			420.50	422.00	D015330	1.50	<0.005		0.001
			422.00	423.50	D015331	1.50	0.039		0.039
423.50	425.00	D015333	1.50	0.128		0.128			
425.00	426.50	D015334	1.50	0.005		0.005			
426.50	428.00	D015335	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
433.22	433.42	CIS  <b>Cisaillement 40°</b> Cisaillement d'intensité moyenne et ayant une épaisseur de 8cm. Il est chloritisé, séricitisé et peu carbonatisé.	428.00	429.50	D015336	1.50	0.184		0.184
			429.50	431.00	D015337	1.50	<0.005		0.001
			431.00	432.50	D015338	1.50	0.005		0.005
			432.50	434.00	D015339	1.50	0.032		0.032
			434.00	435.50	D015340	1.50	0.020		0.020
			435.50	437.00	D015341	1.50	0.038		0.038
			437.00	438.50	D015343	1.50	<0.005		0.001
			438.50	440.00	D015344	1.50	0.126		0.126
			440.00	441.50	D015345	1.50	0.006		0.006
			441.50	443.00	D015346	1.50	<0.005		0.001
			443.00	444.50	D015347	1.50	0.026		0.026
			444.50	446.00	D015348	1.50	0.005		0.005
			446.00	447.50	D015349	1.50	<0.005		0.001
			447.50	449.00	D015350	1.50	<0.005		0.001
			449.00	450.50	D015351	1.50	<0.005		0.001
			450.50	452.00	D015353	1.50	<0.005		0.001
			452.00	453.50	D015354	1.50	0.029		0.029
			453.50	455.00	D015355	1.50	<0.005		0.001
			455.00	456.50	D015356	1.50	<0.005		0.001
			456.50	458.00	D015357	1.50	0.163		0.163
			458.00	459.50	D015358	1.50	1.440		1.440
			459.50	461.00	D015359	1.50	0.761		0.761
			461.00	462.50	D015361	1.50	0.141		0.141
			462.50	464.00	D015363	1.50	0.183		0.183
			464.00	465.50	D015364	1.50	0.977		0.977
			465.50	467.00	D015365	1.50	1.200		1.200
			467.00	468.50	D015366	1.50	0.868		0.868
468.50	470.00	D015367	1.50	0.096		0.096			
470.00	471.50	D015368	1.50	0.197		0.197			
471.50	473.00	D015369	1.50	0.108		0.108			
473.00	474.50	D015370	1.50	0.243		0.243			
474.50	476.00	D015371	1.50	0.089		0.089			
476.00	477.50	D015373	1.50	0.075		0.075			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
476.99	477.13	<p>FAI</p> <p><b>Faille 35°</b></p> <p>Zone de faille ayant environ 6cm en épaisseur, accompagnée de brèche.</p> <p>La chlorite tapisse le plan principal et occupe des fractures.</p>	477.50	479.00	D015374	1.50	0.127		0.127
			479.00	480.50	D015375	1.50	0.009		0.009
			480.50	482.00	D015376	1.50	<0.005		0.001
			482.00	483.50	D015377	1.50	0.017		0.017
			483.50	485.00	D015378	1.50	0.088		0.088
			485.00	486.50	D015379	1.50	<0.005		0.001
			486.50	488.00	D015380	1.50	0.047		0.047
			488.00	489.50	D015381	1.50	0.269		0.269
			489.50	490.95	D015383	1.45	0.112		0.112
490.95	492.32	<p>CIS</p> <p><b>Cisaillement 15°</b></p> <p>Cisaillement intense chloritisé, séricitisé, dont la schistosité est très bien développée et disposée entre 10°-30°ac.</p> <p>Nous observons un système de veinules et veines de quartz-carbonates (roses) chlorite et tourmaline, surtout concordantes à la déformation et variant de 1-2mm à 14cm en épaisseur.</p> <p>En volume, ce système représente environ 50% de la carotte.</p> <p>La tourmaline est surtout amorphe, rarement cristalline. La chlorite tapisse parfois des fractures.</p> <p>Fine pyrite disséminée dans la syénite déformée.</p>	490.95	492.32	D015384	1.37	0.198		0.198
			492.32	494.00	D015385	1.68	0.158		0.158
			494.00	495.50	D015386	1.50	0.298		0.298
			495.50	497.00	D015387	1.50	0.666		0.666
497.00	<p>Fin du sondage</p> <p>Nombre d'échantillons : 338</p> <p>Nombre d'échantillons QAQC : 49</p> <p>Longueur totale échantillonnée : 491.45</p>								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.55	7.00	D015002	A3	1.45	0.603	0.603
18.50	20.00	D015012	D015011	1.50	<0.005	0.001
32.00	33.50	D015022	B4	1.50	2.680	2.680
45.50	47.00	D015032	D015031	1.50	<0.005	0.001
56.00	57.50	D015040	M1	1.50	<0.005	0.001
57.50	59.00	D015042	C4	1.50	1.365	1.365
69.50	71.00	D015052	D015051	1.50	0.033	0.033
83.00	84.50	D015062	D2	1.50	0.848	0.848
96.50	98.00	D015072	D015071	1.50	0.159	0.159
107.00	108.50	D015080	M1	1.50	<0.005	0.001
108.50	110.00	D015082	F2	1.50	8.170	8.490
120.50	122.00	D015092	D015091	1.50	0.561	0.561
132.50	134.00	D015102	G2	1.50	3.850	4.190
146.00	147.50	D015112	D015111	1.50	<0.005	0.001
156.50	158.00	D015120	M1	1.50	<0.005	0.001
158.00	159.50	D015122	H	1.50	0.999	0.999
171.50	173.00	D015132	D015131	1.50	0.024	0.024
185.00	186.50	D015142	A3	1.50	0.609	0.609
198.50	200.00	D015152	D015151	1.50	<0.005	0.001
209.00	210.50	D015160	M1	1.50	<0.005	0.001
210.50	212.00	D015162	B4	1.50	2.630	2.630
224.00	225.50	D015172	D015171	1.50	<0.005	0.001
237.50	239.00	D015182	C4	1.50	1.395	1.395
251.00	252.50	D015192	D015191	1.50	<0.005	0.001
261.50	263.00	D015200	M1	1.50	<0.005	0.001
263.00	264.50	D015202	D2	1.50	0.871	0.871
276.00	277.00	D015212	D015211	1.00	0.012	0.012
288.50	290.00	D015222	F2	1.50	8.170	8.540
302.00	303.50	D015232	D015231	1.50	<0.005	0.001
311.00	312.50	D015240	M1	1.50	<0.005	0.001
312.50	314.00	D015242	G2	1.50	3.710	4.130
326.00	327.50	D015252	D015251	1.50	<0.005	0.001
338.00	339.50	D015262	H	1.50	0.970	0.970



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
340.40	341.90	D015265	M1	1.50	<0.005	0.001
347.00	348.50	D015272	D015271	1.50	0.655	0.655
355.00	356.00	D015280	M1	1.00	<0.005	0.001
356.00	357.50	D015282	A3	1.50	0.580	0.580
369.50	371.00	D015292	D015291	1.50	0.009	0.009
383.00	384.50	D015302	B4	1.50	2.590	2.590
396.50	398.00	D015312	D015311	1.50	<0.005	0.001
407.00	408.50	D015320	M1	1.50	<0.005	0.001
408.50	410.00	D015322	C4	1.50	1.350	1.350
422.00	423.50	D015332	D015331	1.50	0.040	0.040
435.50	437.00	D015342	D2	1.50	0.874	0.874
449.00	450.50	D015352	D015351	1.50	<0.005	0.001
459.50	461.00	D015360	M1	1.50	<0.005	0.001
461.00	462.50	D015362	F2	1.50	8.670	8.490
474.50	476.00	D015372	D015371	1.50	0.082	0.082
488.00	489.50	D015382	G2	1.50	4.180	4.130



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.30°	-55.00°	Non	Reflex	173.00	2.90°	-50.60°	Non
Reflex	77.00	1.30°	-54.80°	Non	Reflex	176.00	2.90°	-50.50°	Non
Reflex	80.00	1.40°	-54.50°	Non	Reflex	179.00	2.70°	-50.50°	Non
Reflex	83.00	1.50°	-54.10°	Non	Reflex	182.00	2.80°	-50.50°	Non
Reflex	86.00	1.60°	-53.70°	Non	Reflex	185.00	3.40°	-50.50°	Non
Reflex	89.00	3.00°	-53.30°	Non	Reflex	188.00	3.50°	-50.50°	Non
Reflex	92.00	2.90°	-53.00°	Non	Reflex	191.00	3.30°	-50.60°	Non
Reflex	95.00	4.60°	-52.70°	Oui	Reflex	194.00	3.30°	-50.50°	Non
Reflex	98.00	3.00°	-52.50°	Non	Reflex	197.00	3.50°	-50.60°	Non
Reflex	101.00	6.80°	-52.30°	Oui	Reflex	200.00	3.80°	-50.40°	Non
Reflex	104.00	2.60°	-51.80°	Non	Reflex	203.00	3.90°	-50.10°	Non
Reflex	107.00	3.00°	-51.70°	Non	Reflex	206.00	3.90°	-50.00°	Non
Reflex	110.00	3.00°	-51.60°	Non	Reflex	209.00	4.00°	-49.90°	Non
Reflex	113.00	2.80°	-51.60°	Non	Reflex	212.00	4.10°	-49.80°	Non
Reflex	116.00	2.80°	-51.60°	Non	Reflex	215.00	4.30°	-49.80°	Non
Reflex	119.00	3.20°	-51.50°	Non	Reflex	218.00	4.20°	-49.80°	Non
Reflex	122.00	2.80°	-51.40°	Non	Reflex	221.00	4.30°	-49.80°	Non
Reflex	125.00	2.70°	-51.30°	Non	Reflex	224.00	4.40°	-49.80°	Non
Reflex	128.00	2.60°	-51.30°	Non	Reflex	227.00	5.30°	-49.80°	Non
Reflex	131.00	2.40°	-51.20°	Non	Reflex	230.00	5.50°	-49.80°	Non
Reflex	134.00	2.30°	-51.20°	Non	Reflex	233.00	4.80°	-49.70°	Non
Reflex	137.00	2.30°	-51.10°	Non	Reflex	236.00	4.40°	-49.70°	Non
Reflex	140.00	2.30°	-51.10°	Non	Reflex	239.00	4.20°	-49.70°	Non
Reflex	143.00	2.40°	-51.10°	Non	Reflex	242.00	4.30°	-49.70°	Non
Reflex	146.00	2.30°	-51.00°	Non	Reflex	245.00	4.10°	-49.50°	Non
Reflex	149.00	2.40°	-50.90°	Non	Reflex	248.00	4.20°	-49.50°	Non
Reflex	152.00	2.50°	-50.90°	Non	Reflex	251.00	4.10°	-49.50°	Non
Reflex	155.00	2.50°	-50.80°	Non	Reflex	254.00	4.00°	-49.50°	Non
Reflex	158.00	2.60°	-50.80°	Non	Reflex	257.00	4.10°	-49.50°	Non
Reflex	161.00	2.90°	-50.70°	Non	Reflex	260.00	6.00°	-49.40°	Oui
Reflex	164.00	2.80°	-50.70°	Non	Reflex	263.00	3.70°	-49.30°	Non
Reflex	167.00	2.80°	-50.60°	Non	Reflex	266.00	3.70°	-49.20°	Non
Reflex	170.00	2.90°	-50.60°	Non	Reflex	269.00	4.50°	-49.00°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	2.30°	-49.10°	Non	Reflex	371.00	7.30°	-48.30°	Non
Reflex	275.00	3.50°	-49.00°	Non	Reflex	374.00	7.30°	-48.30°	Non
Reflex	278.00	5.60°	-48.90°	Non	Reflex	377.00	9.40°	-48.30°	Non
Reflex	281.00	5.60°	-49.00°	Non	Reflex	380.00	8.70°	-48.20°	Non
Reflex	284.00	5.80°	-48.90°	Non	Reflex	383.00	9.00°	-48.20°	Non
Reflex	287.00	6.00°	-48.90°	Non	Reflex	386.00	8.90°	-48.20°	Non
Reflex	290.00	4.70°	-48.90°	Non	Reflex	389.00	8.30°	-48.20°	Non
Reflex	293.00	5.70°	-48.90°	Non	Reflex	392.00	10.80°	-48.20°	Oui
Reflex	296.00	6.50°	-48.90°	Non	Reflex	395.00	9.40°	-48.20°	Non
Reflex	299.00	6.10°	-48.80°	Non	Reflex	398.00	8.20°	-48.20°	Non
Reflex	302.00	5.90°	-48.80°	Non	Reflex	401.00	7.60°	-48.20°	Non
Reflex	305.00	6.10°	-48.70°	Non	Reflex	404.00	9.70°	-48.20°	Non
Reflex	308.00	6.50°	-48.70°	Non	Reflex	407.00	9.00°	-48.20°	Non
Reflex	311.00	5.80°	-48.70°	Non	Reflex	410.00	8.70°	-48.20°	Non
Reflex	314.00	6.40°	-48.70°	Non	Reflex	413.00	9.10°	-48.20°	Non
Reflex	317.00	5.10°	-48.70°	Non	Reflex	416.00	8.50°	-48.10°	Non
Reflex	320.00	4.90°	-48.60°	Non	Reflex	419.00	9.30°	-48.10°	Non
Reflex	323.00	5.20°	-48.60°	Non	Reflex	422.00	7.40°	-48.10°	Non
Reflex	326.00	4.10°	-48.50°	Non	Reflex	425.00	9.60°	-48.10°	Non
Reflex	329.00	6.80°	-48.50°	Non	Reflex	428.00	8.70°	-48.10°	Non
Reflex	332.00	7.00°	-48.50°	Non	Reflex	431.00	9.60°	-48.10°	Non
Reflex	335.00	10.10°	-48.40°	Oui	Reflex	434.00	8.30°	-48.10°	Non
Reflex	338.00	6.40°	-48.40°	Non	Reflex	437.00	10.90°	-48.00°	Non
Reflex	341.00	6.60°	-48.40°	Non	Reflex	440.00	10.10°	-48.00°	Non
Reflex	344.00	6.10°	-48.40°	Non	Reflex	443.00	9.40°	-48.00°	Non
Reflex	347.00	9.10°	-48.40°	Non	Reflex	446.00	10.00°	-48.00°	Non
Reflex	350.00	10.00°	-48.40°	Non	Reflex	449.00	7.30°	-48.00°	Oui
Reflex	353.00	8.90°	-48.40°	Non	Reflex	452.00	9.30°	-48.00°	Non
Reflex	356.00	9.20°	-48.40°	Non	Reflex	455.00	9.40°	-47.90°	Non
Reflex	359.00	7.00°	-48.40°	Non	Reflex	458.00	10.00°	-47.90°	Non
Reflex	362.00	6.70°	-48.40°	Non	Reflex	461.00	8.70°	-47.90°	Non
Reflex	365.00	8.10°	-48.40°	Non	Reflex	464.00	6.70°	-47.90°	Non
Reflex	368.00	7.00°	-48.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT						
		<b>Mort-terrain</b>						
2.50	101.30	BA; AMY; FIN; COU	2.50	4.00	D006411	1.50	0.006	0.006
		<b>Basalte andésitique; Amygdalaire; Grains fins; Coussiné</b>	4.00	5.50	D006412	1.50	0.348	0.348
		Basalte andésitique avec passage à grains fins à moyens, amygdalaire et coussiné.	5.50	7.00	D006413	1.50	<0.005	0.001
			7.00	8.50	D006414	1.50	<0.005	0.001
			8.50	10.00	D006415	1.50	<0.005	0.001
			10.00	11.50	D006416	1.50	0.027	0.027
			11.50	13.00	D006418	1.50	0.007	0.007
			13.00	14.00	D006419	1.00	0.015	0.015
			14.00	15.20	D006420	1.20	0.014	0.014
			15.20	16.00	D006421	0.80	2.090	2.090
			16.00	17.00	D006422	1.00	0.009	0.009
			17.00	18.00	D006423	1.00	0.047	0.047
			18.00	19.50	D006424	1.50	0.031	0.031
			19.50	21.00	D006425	1.50	0.060	0.060
			21.00	22.50	D006426	1.50	0.063	0.063
			22.50	23.80	D006428	1.30	0.373	0.373
			23.80	25.00	D006429	1.20	0.334	0.334
			25.00	26.50	D006430	1.50	<0.005	0.001
			26.50	28.00	D006431	1.50	0.030	0.030
			28.00	29.50	D006432	1.50	<0.005	0.001
			29.50	31.00	D006433	1.50	0.034	0.034
			31.00	32.50	D006434	1.50	<0.005	0.001
			32.50	34.00	D006435	1.50	<0.005	0.001
			34.00	35.50	D006436	1.50	0.435	0.435
			35.50	37.00	D006438	1.50	0.013	0.013
			37.00	38.50	D006439	1.50	0.006	0.006
			38.50	40.00	D006440	1.50	<0.005	0.001
			40.00	41.50	D006441	1.50	0.006	0.006
			41.50	43.00	D006443	1.50	0.843	0.843
			43.00	44.50	D006444	1.50	0.028	0.028
			44.50	46.00	D006445	1.50	0.572	0.572
			46.00	47.50	D006446	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	47.50	49.00	D006448	1.50	0.006		0.006
	49.00	50.50	D006449	1.50	0.006		0.006
	50.50	52.00	D006450	1.50	0.006		0.006
	52.00	53.50	D006451	1.50	<0.005		0.001
	53.50	55.00	D006452	1.50	0.016		0.016
	55.00	56.50	D006453	1.50	1.855		1.855
	56.50	58.00	D006454	1.50	0.063		0.063
	58.00	59.50	D006455	1.50	0.225		0.225
	59.50	61.00	D006456	1.50	0.011		0.011
	61.00	62.50	D006458	1.50	0.006		0.006
	62.50	64.00	D006459	1.50	0.005		0.005
	64.00	65.00	D006460	1.00	0.007		0.007
	65.00	66.00	D006461	1.00	1.420		1.420
	66.00	67.00	D006462	1.00	0.012		0.012
	67.00	68.50	D006463	1.50	0.157		0.157
	68.50	70.00	D006464	1.50	1.005		1.005
	70.00	71.50	D006465	1.50	0.435		0.435
	71.50	73.00	D006466	1.50	0.007		0.007
	73.00	74.50	D006468	1.50	0.008		0.008
	74.50	76.00	D006469	1.50	0.010		0.010
	76.00	77.00	D006470	1.00	0.006		0.006
	77.00	78.00	D006471	1.00	<0.005		0.001
	78.00	79.50	D006472	1.50	0.007		0.007
	79.50	81.00	D006473	1.50	<0.005		0.001
	81.00	82.50	D006474	1.50	<0.005		0.001
	82.50	84.00	D006475	1.50	<0.005		0.001
	84.00	85.50	D006476	1.50	<0.005		0.001
	85.50	87.00	D006478	1.50	<0.005		0.001
	87.00	88.50	D006479	1.50	<0.005		0.001
	88.50	90.00	D006480	1.50	0.123		0.123
	90.00	91.50	D006481	1.50	<0.005		0.001
	91.50	93.00	D006483	1.50	<0.005		0.001
	93.00	94.50	D006484	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
101.30	106.00	SY; FIN; MTY <b>Syénite 55°; Grains fins; Grains moyens</b> Syénite à grains fins à grains moyens avec passage de peu phénocristaux Xmm, localement MG+.	94.50	96.00	D006485	1.50	<0.005		0.001
			96.00	97.50	D006486	1.50	<0.005		0.001
			97.50	99.00	D006488	1.50	0.037		0.037
			99.00	100.00	D006489	1.00	<0.005		0.001
			100.00	101.30	D006490	1.30	0.029		0.029
			101.30	102.50	D006491	1.20	0.019		0.019
			102.50	104.00	D006492	1.50	0.111		0.111
			104.00	105.00	D006493	1.00	<0.005		0.001
			105.00	106.00	D006494	1.00	0.007		0.007
			106.00	109.00	BA; AMY; FIN <b>Basalte andésitique 50°; Amygdalaire; Grains fins</b> Basalte andésitique, amygdalaire à grains fins et faiblement cisailé.	106.00	107.50	D006495	1.50
107.50	109.00	D006496				1.50	0.062		0.062
109.00	284.30	SY; FIN <b>Syénite; Grains fins</b> Syénite à grains fins à grains moyens avec passage de qlq phénocristaux Xmm, localement MG+.	109.00	110.50	D006498	1.50	0.009		0.009
			110.50	111.50	D006499	1.00	0.067		0.067
			111.50	113.00	D006500	1.50	0.015		0.015
			113.00	114.50	D006501	1.50	0.014		0.014
			114.50	116.00	D006502	1.50	<0.005		0.001
			116.00	117.50	D006503	1.50	<0.005		0.001
			117.50	119.00	D006504	1.50	<0.005		0.001
			119.00	120.50	D006505	1.50	<0.005		0.001
			120.50	122.00	D006506	1.50	<0.005		0.001
			122.00	123.50	D006508	1.50	0.007		0.007
			123.50	125.00	D006509	1.50	0.012		0.012
			125.00	126.00	D006510	1.00	<0.005		0.001
			126.00	127.50	D006511	1.50	0.017		0.017
			127.50	129.00	D006512	1.50	0.363		0.363
			129.00	130.50	D006513	1.50	0.056		0.056
			130.50	132.00	D006514	1.50	<0.005		0.001
			132.00	133.00	D006515	1.00	0.033		0.033
			133.00	134.50	D006516	1.50	0.526		0.526
			134.50	136.00	D006518	1.50	<0.005		0.001
			136.00	137.50	D006519	1.50	0.038		0.038
137.50	138.50	D006520	1.00	<0.005		0.001			
138.50	140.00	D006521	1.50	0.206		0.206			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	140.00	141.50	D006523	1.50	0.173		0.173
	141.50	143.00	D006524	1.50	0.114		0.114
	143.00	144.50	D006525	1.50	0.211		0.211
	144.50	146.00	D006526	1.50	0.056		0.056
	146.00	147.50	D006528	1.50	0.163		0.163
	147.50	149.00	D006529	1.50	0.215		0.215
	149.00	150.50	D006530	1.50	0.179		0.179
	150.50	152.00	D006531	1.50	0.012		0.012
	152.00	153.50	D006532	1.50	0.020		0.020
	153.50	155.00	D006533	1.50	0.178		0.178
	155.00	156.50	D006534	1.50	0.069		0.069
	156.50	158.00	D006535	1.50	0.363		0.363
	158.00	159.50	D006536	1.50	0.069		0.069
	159.50	161.00	D006538	1.50	0.049		0.049
	161.00	162.50	D006539	1.50	<0.005		0.001
	162.50	164.00	D006540	1.50	<0.005		0.001
	164.00	165.50	D006541	1.50	<0.005		0.001
	165.50	167.00	D006542	1.50	0.015		0.015
	167.00	168.50	D006543	1.50	<0.005		0.001
	168.50	170.00	D006544	1.50	<0.005		0.001
	170.00	171.50	D006545	1.50	0.153		0.153
	171.50	173.00	D006546	1.50	0.082		0.082
	173.00	174.50	D006548	1.50	0.654		0.654
	174.50	176.00	D006549	1.50	1.750		1.750
	176.00	177.50	D006550	1.50	0.961		0.961
	177.50	179.00	D006551	1.50	0.342		0.342
	179.00	180.00	D006552	1.00	0.136		0.136
	180.00	181.00	D006553	1.00	0.973		0.973
	181.00	182.00	D006554	1.00	0.356		0.356
	182.00	183.50	D006555	1.50	1.755		1.755
	183.50	185.00	D006556	1.50	2.200		2.200
	185.00	186.50	D006558	1.50	0.005		0.005
	186.50	188.00	D006559	1.50	0.060		0.060



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	188.00	189.50	D006560	1.50	0.005		0.005
	189.50	191.00	D006561	1.50	0.034		0.034
	191.00	192.50	D006563	1.50	0.242		0.242
	192.50	194.00	D006564	1.50	1.595		1.595
	194.00	195.50	D006565	1.50	0.137		0.137
	195.50	197.00	D006566	1.50	2.320		2.320
	197.00	198.50	D006568	1.50	0.011		0.011
	198.50	200.00	D006569	1.50	0.096		0.096
	200.00	201.50	D006570	1.50	0.260		0.260
	201.50	203.00	D006571	1.50	0.246		0.246
	203.00	204.50	D006572	1.50	0.087		0.087
	204.50	206.00	D006573	1.50	>10.0	24.00	24.000
	206.00	207.50	D006574	1.50	0.099		0.099
	207.50	209.00	D006575	1.50	0.024		0.024
	209.00	210.50	D006576	1.50	0.026		0.026
	210.50	212.00	D006578	1.50	0.125		0.125
	212.00	213.50	D006579	1.50	0.075		0.075
	213.50	215.00	D006580	1.50	0.061		0.061
	215.00	216.50	D006581	1.50	0.284		0.284
	216.50	218.00	D006582	1.50	0.095		0.095
	218.00	219.50	D006583	1.50	0.252		0.252
	219.50	221.00	D006584	1.50	0.213		0.213
	221.00	222.50	D006585	1.50	0.194		0.194
	222.50	224.00	D006586	1.50	0.345		0.345
	224.00	225.50	D006588	1.50	0.017		0.017
	225.50	227.00	D006589	1.50	0.147		0.147
	227.00	228.50	D006590	1.50	0.072		0.072
	228.50	230.00	D006591	1.50	0.023		0.023
	230.00	231.50	D006592	1.50	0.025		0.025
	231.50	233.00	D006593	1.50	0.219		0.219
	233.00	234.50	D006594	1.50	0.039		0.039
	234.50	236.00	D006595	1.50	0.087		0.087
	236.00	237.50	D006596	1.50	0.026		0.026

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	237.50	239.00	D006598	1.50	0.133		0.133
	239.00	240.50	D006599	1.50	<0.005		0.001
	240.50	242.00	D006600	1.50	0.009		0.009
	242.00	243.50	D006601	1.50	0.007		0.007
	243.50	245.00	D006603	1.50	0.009		0.009
	245.00	246.50	D006604	1.50	0.157		0.157
	246.50	248.00	D006605	1.50	0.016		0.016
	248.00	249.00	D006606	1.00	0.015		0.015
	249.00	250.20	D006608	1.20	<0.005		0.001
	250.20	251.50	D006609	1.30	0.019		0.019
	251.50	253.00	D006610	1.50	0.013		0.013
	253.00	254.50	D006611	1.50	<0.005		0.001
	254.50	256.00	D006612	1.50	0.282		0.282
	256.00	257.50	D006613	1.50	0.995		0.995
	257.50	259.00	D006614	1.50	0.016		0.016
	259.00	260.50	D006615	1.50	0.224		0.224
	260.50	262.00	D006616	1.50	0.140		0.140
	262.00	263.00	D006618	1.00	0.055		0.055
	263.00	264.00	D006619	1.00	0.671		0.671
	264.00	265.50	D006620	1.50	<0.005		0.001
	265.50	267.00	D006621	1.50	0.163		0.163
	267.00	268.00	D006622	1.00	0.920		0.920
	268.00	269.50	D006623	1.50	0.620		0.620
	269.50	271.00	D006624	1.50	0.013		0.013
	271.00	272.50	D006625	1.50	0.449		0.449
	272.50	274.00	D006626	1.50	0.422		0.422
	274.00	275.50	D006628	1.50	0.192		0.192
	275.50	277.00	D006629	1.50	0.939		0.939
	277.00	278.50	D006630	1.50	0.060		0.060
	278.50	280.00	D006631	1.50	1.750		1.750
	280.00	281.50	D006632	1.50	7.890	7.84	7.840
	281.50	283.00	D006633	1.50	0.019		0.019
	283.00	284.30	D006634	1.30	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
284.30	320.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique à grains fins avec de phénocristaux Xmm à Xcm et MG++.	284.30	285.50	D006635	1.20	<0.005		0.001
			285.50	287.00	D006636	1.50	<0.005		0.001
			287.00	288.50	D006638	1.50	0.012		0.012
			288.50	290.00	D006639	1.50	<0.005		0.001
			290.00	291.50	D006640	1.50	<0.005		0.001
			291.50	293.00	D006641	1.50	<0.005		0.001
			293.00	294.50	D006643	1.50	0.048		0.048
			294.50	296.00	D006644	1.50	0.006		0.006
			296.00	297.50	D006645	1.50	0.008		0.008
			297.50	299.00	D006646	1.50	0.011		0.011
			299.00	300.50	D006648	1.50	0.011		0.011
			300.50	302.00	D006649	1.50	0.133		0.133
			302.00	303.50	D006650	1.50	0.025		0.025
			303.50	305.00	D006651	1.50	0.021		0.021
			305.00	306.50	D006652	1.50	0.006		0.006
			306.50	308.00	D006653	1.50	0.005		0.005
			308.00	309.50	D006654	1.50	0.011		0.011
			309.50	311.00	D006655	1.50	0.011		0.011
			311.00	312.50	D006656	1.50	0.050		0.050
			312.50	314.00	D006658	1.50	0.511		0.511
314.00	315.50	D006659	1.50	<0.005		0.001			
315.50	317.00	D006660	1.50	<0.005		0.001			
317.00	318.50	D006661	1.50	<0.005		0.001			
318.50	320.00	D006662	1.50	0.067		0.067			
320.00	470.00	SY; FIN <b>Syénite; Grains fins</b> Syénite à grains fins à grains moyens avec passage de qlq phénocristaux Xmm reparti inégalement, sporadiquement MG++.	320.00	321.50	D006663	1.50	<0.005		0.001
			321.50	323.00	D006664	1.50	0.014		0.014
			323.00	324.50	D006665	1.50	<0.005		0.001
			324.50	326.00	D006666	1.50	0.019		0.019
			326.00	327.50	D006668	1.50	0.029		0.029
			327.50	329.00	D006669	1.50	1.130		1.130
			329.00	330.50	D006670	1.50	0.060		0.060
			330.50	332.00	D006671	1.50	0.012		0.012
			332.00	333.50	D006672	1.50	0.229		0.229

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	333.50	335.00	D006673	1.50	<0.005		0.001
	335.00	336.50	D006674	1.50	<0.005		0.001
	336.50	338.00	D006675	1.50	<0.005		0.001
	338.00	339.50	D006676	1.50	0.030		0.030
	339.50	341.00	D006678	1.50	0.018		0.018
	341.00	342.50	D006679	1.50	0.021		0.021
	342.50	344.00	D006680	1.50	<0.005		0.001
	344.00	345.50	D006681	1.50	<0.005		0.001
	345.50	347.00	D006683	1.50	<0.005		0.001
	347.00	348.50	D006684	1.50	<0.005		0.001
	348.50	350.00	D006685	1.50	0.055		0.055
	350.00	351.50	D006686	1.50	0.164		0.164
	351.50	353.00	D006688	1.50	0.126		0.126
	353.00	354.50	D006689	1.50	0.038		0.038
	354.50	356.00	D006690	1.50	0.036		0.036
	356.00	357.50	D006691	1.50	0.092		0.092
	357.50	359.00	D006692	1.50	0.367		0.367
	359.00	360.50	D006693	1.50	0.012		0.012
	360.50	362.00	D006694	1.50	0.064		0.064
	362.00	363.50	D006695	1.50	0.022		0.022
	363.50	365.00	D006696	1.50	0.038		0.038
	365.00	366.50	D006698	1.50	0.109		0.109
	366.50	368.00	D006699	1.50	0.014		0.014
	368.00	369.50	D006700	1.50	<0.005		0.001
	369.50	371.00	D006701	1.50	0.078		0.078
	371.00	372.50	D006703	1.50	0.032		0.032
	372.50	374.00	D006704	1.50	0.011		0.011
	374.00	375.50	D006705	1.50	1.910		1.910
	375.50	377.00	D006706	1.50	0.277		0.277
	377.00	378.50	D006708	1.50	0.197		0.197
	378.50	380.00	D006709	1.50	0.033		0.033
	380.00	381.50	D006710	1.50	0.019		0.019
	381.50	383.00	D006711	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	383.00	384.50	D006712	1.50	2.280		2.280
	384.50	386.00	D006713	1.50	0.095		0.095
	386.00	387.50	D006714	1.50	0.005		0.005
	387.50	389.00	D006715	1.50	0.135		0.135
	389.00	390.50	D006716	1.50	0.457		0.457
	390.50	392.00	D006718	1.50	0.097		0.097
	392.00	393.50	D006719	1.50	0.222		0.222
	393.50	395.00	D006720	1.50	0.043		0.043
	395.00	396.50	D006721	1.50	0.051		0.051
	396.50	398.00	D006722	1.50	0.030		0.030
	398.00	399.50	D006723	1.50	0.050		0.050
	399.50	401.00	D006724	1.50	0.020		0.020
	401.00	402.50	D006725	1.50	0.132		0.132
	402.50	404.00	D006726	1.50	0.110		0.110
	404.00	405.50	D006728	1.50	0.025		0.025
	405.50	407.00	D006729	1.50	0.556		0.556
	407.00	408.50	D006730	1.50	0.036		0.036
	408.50	410.00	D006731	1.50	0.017		0.017
	410.00	411.50	D006732	1.50	0.177		0.177
	411.50	413.00	D006733	1.50	0.037		0.037
	413.00	414.50	D006734	1.50	0.009		0.009
	414.50	416.00	D006735	1.50	0.011		0.011
	416.00	417.50	D006736	1.50	0.030		0.030
	417.50	419.00	D006738	1.50	0.038		0.038
	419.00	420.00	D006739	1.00	1.650		1.650
	420.00	421.50	D006740	1.50	0.231		0.231
	421.50	423.00	D006741	1.50	0.019		0.019
	423.00	424.50	D006743	1.50	<0.005		0.001
	424.50	426.00	D006744	1.50	1.095		1.095
	426.00	427.50	D006745	1.50	<0.005		0.001
	427.50	429.00	D006746	1.50	<0.005		0.001
	429.00	430.50	D006748	1.50	0.226		0.226
	430.50	432.00	D006749	1.50	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	432.00	433.50	D006750	1.50	0.010		0.010
	433.50	435.00	D006751	1.50	<0.005		0.001
	435.00	436.50	D006752	1.50	<0.005		0.001
	436.50	438.00	D006753	1.50	0.006		0.006
	438.00	439.50	D006754	1.50	<0.005		0.001
	439.50	441.00	D006755	1.50	<0.005		0.001
	441.00	442.50	D006756	1.50	<0.005		0.001
	442.50	444.00	D006758	1.50	<0.005		0.001
	444.00	445.50	D006759	1.50	<0.005		0.001
	445.50	447.00	D006760	1.50	0.167		0.167
	447.00	448.50	D006761	1.50	0.009		0.009
	448.50	450.00	D006762	1.50	0.134		0.134
	450.00	451.50	D006763	1.50	0.721		0.721
	451.50	453.00	D006764	1.50	0.031		0.031
	453.00	454.50	D006765	1.50	0.030		0.030
	454.50	456.00	D006766	1.50	0.038		0.038
	456.00	457.50	D006768	1.50	0.215		0.215
	457.50	459.00	D006769	1.50	0.141		0.141
	459.00	460.50	D006770	1.50	0.005		0.005
	460.50	462.00	D006771	1.50	<0.005		0.001
	462.00	463.50	D006772	1.50	<0.005		0.001
	463.50	465.00	D006773	1.50	<0.005		0.001
	465.00	466.50	D006774	1.50	<0.005		0.001
	466.50	468.00	D006775	1.50	0.192		0.192
	468.00	469.00	D006776	1.00	1.430		1.430
	469.00	470.00	D006778	1.00	0.007		0.007
470.00	Fin du sondage Nombre d'échantillons : 322 Nombre d'échantillons QAQC : 46 Longueur totale échantillonnée : 467.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.00	11.50	D006417	D006416	1.50	0.032	0.032
21.00	22.50	D006427	A3	1.50	0.599	0.599
34.00	35.50	D006437	D006436	1.50	0.468	0.468
40.00	41.50	D006442	M1	1.50	<0.005	0.001
46.00	47.50	D006447	G2	1.50	4.030	4.250
59.50	61.00	D006457	D006456	1.50	0.012	0.012
71.50	73.00	D006467	C4	1.50	1.355	1.355
84.00	85.50	D006477	D006476	1.50	<0.005	0.001
90.00	91.50	D006482	M1	1.50	<0.005	0.001
96.00	97.50	D006487	D2	1.50	0.833	0.833
107.50	109.00	D006497	D006496	1.50	0.072	0.072
120.50	122.00	D006507	F2	1.50	8.330	8.270
133.00	134.50	D006517	D006516	1.50	0.537	0.537
138.50	140.00	D006522	M1	1.50	<0.005	0.001
144.50	146.00	D006527	G2	1.50	4.010	4.020
158.00	159.50	D006537	D006536	1.50	0.052	0.052
171.50	173.00	D006547	H	1.50	0.986	0.986
183.50	185.00	D006557	D006556	1.50	2.110	2.110
189.50	191.00	D006562	M1	1.50	<0.005	0.001
195.50	197.00	D006567	A3	1.50	0.585	0.585
209.00	210.50	D006577	D006576	1.50	0.054	0.054
222.50	224.00	D006587	B4	1.50	2.160	2.160
236.00	237.50	D006597	D006596	1.50	0.020	0.020
242.00	243.50	D006602	M1	1.50	<0.005	0.001
248.00	249.00	D006607	C4	1.00	1.315	1.315
260.50	262.00	D006617	D006616	1.50	0.125	0.125
272.50	274.00	D006627	D2	1.50	0.851	0.851
285.50	287.00	D006637	D006636	1.50	<0.005	0.001
291.50	293.00	D006642	M1	1.50	<0.005	0.001
297.50	299.00	D006647	F2	1.50	8.450	8.220
311.00	312.50	D006657	D006656	1.50	0.049	0.049
324.50	326.00	D006667	G2	1.50	3.960	4.060
338.00	339.50	D006677	D006676	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
344.00	345.50	D006682	M1	1.50	<0.005	0.001
350.00	351.50	D006687	H	1.50	0.972	0.972
363.50	365.00	D006697	D006696	1.50	0.035	0.035
369.50	371.00	D006702	M1	1.50	<0.005	0.001
375.50	377.00	D006707	A3	1.50	0.584	0.584
389.00	390.50	D006717	D006716	1.50	0.451	0.451
402.50	404.00	D006727	H	1.50	0.978	0.978
416.00	417.50	D006737	D006736	1.50	0.031	0.031
421.50	423.00	D006742	M1	1.50	<0.005	0.001
427.50	429.00	D006747	D2	1.50	0.880	0.880
441.00	442.50	D006757	D006756	1.50	<0.005	0.001
454.50	456.00	D006767	B4	1.50	2.570	2.570
468.00	469.00	D006777	D006776	1.00	1.715	1.715



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-131**

Titre minier :

Section :                      631300

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    Guy gbaguidi

Lot :

Du :                              2010-03-18

Date de description :

Au :                              2010-03-22

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                    464.00 m

Est	631 299.7
Nord	5 374 200.0
Élévation	299.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	352.40°	-60.10°	Oui
Reflex	5.00	358.40°	-60.10°	Non
Reflex	8.00	358.90°	-60.10°	Non
Reflex	11.00	358.70°	-60.10°	Non
Reflex	14.00	358.50°	-60.10°	Non
Reflex	17.00	358.40°	-60.10°	Non
Reflex	20.00	358.40°	-60.10°	Non
Reflex	23.00	358.40°	-60.10°	Non
Reflex	26.00	358.30°	-60.10°	Non
Reflex	29.00	358.40°	-60.10°	Non
Reflex	32.00	358.40°	-60.10°	Non
Reflex	35.00	358.40°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.60°	-60.20°	Non
Reflex	41.00	358.60°	-60.20°	Non
Reflex	44.00	358.80°	-60.20°	Non
Reflex	47.00	358.50°	-60.00°	Non
Reflex	50.00	358.40°	-59.90°	Non
Reflex	53.00	358.30°	-59.90°	Non
Reflex	56.00	358.10°	-59.90°	Non
Reflex	59.00	358.50°	-59.90°	Non
Reflex	62.00	358.00°	-59.70°	Non
Reflex	65.00	357.80°	-59.70°	Non
Reflex	68.00	357.70°	-59.50°	Non
Reflex	71.00	357.80°	-59.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	357.70°	-59.60°	Non	Reflex	173.00	359.40°	-58.50°	Non
Reflex	77.00	358.10°	-59.50°	Non	Reflex	176.00	0.40°	-58.60°	Non
Reflex	80.00	358.00°	-59.50°	Non	Reflex	179.00	359.80°	-58.60°	Non
Reflex	83.00	358.10°	-59.50°	Non	Reflex	182.00	358.80°	-58.50°	Non
Reflex	86.00	357.10°	-59.40°	Non	Reflex	185.00	359.00°	-58.50°	Non
Reflex	89.00	358.30°	-59.40°	Non	Reflex	188.00	0.40°	-58.50°	Non
Reflex	92.00	358.50°	-59.30°	Non	Reflex	191.00	1.70°	-58.50°	Non
Reflex	95.00	358.70°	-59.40°	Non	Reflex	194.00	1.70°	-58.40°	Non
Reflex	98.00	358.70°	-59.40°	Non	Reflex	197.00	2.20°	-58.40°	Non
Reflex	101.00	358.90°	-59.40°	Non	Reflex	200.00	2.10°	-58.40°	Non
Reflex	104.00	358.60°	-59.30°	Non	Reflex	203.00	0.90°	-58.40°	Oui
Reflex	107.00	358.60°	-59.30°	Non	Reflex	206.00	2.50°	-58.40°	Non
Reflex	110.00	359.30°	-59.20°	Non	Reflex	209.00	2.60°	-58.40°	Non
Reflex	113.00	359.10°	-59.10°	Non	Reflex	212.00	2.90°	-58.40°	Non
Reflex	116.00	359.10°	-58.90°	Non	Reflex	215.00	2.40°	-58.40°	Non
Reflex	119.00	359.10°	-58.90°	Non	Reflex	218.00	2.20°	-58.40°	Non
Reflex	122.00	358.10°	-58.90°	Non	Reflex	221.00	2.20°	-58.40°	Non
Reflex	125.00	359.10°	-59.00°	Non	Reflex	224.00	2.10°	-58.40°	Non
Reflex	128.00	359.20°	-58.90°	Non	Reflex	227.00	2.10°	-58.40°	Non
Reflex	131.00	359.30°	-58.90°	Non	Reflex	230.00	2.20°	-58.40°	Non
Reflex	134.00	359.40°	-58.90°	Non	Reflex	233.00	2.20°	-58.40°	Non
Reflex	137.00	359.50°	-58.90°	Non	Reflex	236.00	2.10°	-58.30°	Non
Reflex	140.00	359.50°	-58.80°	Non	Reflex	239.00	2.20°	-58.40°	Non
Reflex	143.00	359.70°	-58.90°	Non	Reflex	242.00	2.30°	-58.30°	Non
Reflex	146.00	359.80°	-58.90°	Non	Reflex	245.00	2.30°	-58.30°	Non
Reflex	149.00	0.00°	-58.80°	Non	Reflex	248.00	2.40°	-58.30°	Non
Reflex	152.00	0.20°	-58.70°	Non	Reflex	251.00	2.20°	-58.30°	Non
Reflex	155.00	0.40°	-58.80°	Non	Reflex	254.00	3.00°	-58.30°	Non
Reflex	158.00	0.60°	-58.80°	Non	Reflex	257.00	2.40°	-58.30°	Non
Reflex	161.00	1.80°	-58.70°	Non	Reflex	260.00	3.20°	-58.40°	Non
Reflex	164.00	2.10°	-58.70°	Non	Reflex	263.00	2.60°	-58.30°	Non
Reflex	167.00	2.30°	-58.70°	Non	Reflex	266.00	2.60°	-58.30°	Non
Reflex	170.00	359.00°	-58.60°	Non	Reflex	269.00	3.00°	-58.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	2.30°	-58.30°	Non	Reflex	371.00	6.20°	-58.70°	Non
Reflex	275.00	2.50°	-58.40°	Non	Reflex	374.00	5.70°	-58.60°	Non
Reflex	278.00	2.30°	-58.40°	Non	Reflex	377.00	5.00°	-58.70°	Non
Reflex	281.00	2.30°	-58.40°	Non	Reflex	380.00	4.80°	-58.60°	Non
Reflex	284.00	2.60°	-58.40°	Non	Reflex	383.00	5.00°	-58.60°	Non
Reflex	287.00	3.40°	-58.40°	Non	Reflex	386.00	5.20°	-58.60°	Non
Reflex	290.00	3.00°	-58.40°	Non	Reflex	389.00	5.30°	-58.60°	Non
Reflex	293.00	3.20°	-58.40°	Non	Reflex	392.00	5.40°	-58.60°	Non
Reflex	296.00	3.80°	-58.50°	Non	Reflex	395.00	5.70°	-58.70°	Non
Reflex	299.00	3.00°	-58.40°	Non	Reflex	398.00	5.80°	-58.60°	Non
Reflex	302.00	3.10°	-58.50°	Non	Reflex	401.00	5.90°	-58.70°	Non
Reflex	305.00	3.10°	-58.50°	Non	Reflex	404.00	6.10°	-58.60°	Non
Reflex	308.00	3.10°	-58.50°	Non	Reflex	407.00	5.70°	-58.60°	Non
Reflex	311.00	3.50°	-58.50°	Non	Reflex	410.00	6.30°	-58.60°	Non
Reflex	314.00	3.70°	-58.50°	Non	Reflex	413.00	6.10°	-58.60°	Non
Reflex	317.00	3.30°	-58.50°	Non	Reflex	416.00	7.40°	-58.60°	Oui
Reflex	320.00	3.10°	-58.50°	Non	Reflex	419.00	6.50°	-58.70°	Non
Reflex	323.00	5.30°	-58.60°	Non	Reflex	422.00	6.30°	-58.70°	Non
Reflex	326.00	3.70°	-58.60°	Non	Reflex	425.00	6.10°	-58.60°	Non
Reflex	329.00	4.10°	-58.60°	Non	Reflex	428.00	6.10°	-58.60°	Non
Reflex	332.00	4.20°	-58.60°	Non	Reflex	431.00	6.30°	-58.60°	Non
Reflex	335.00	4.10°	-58.60°	Non	Reflex	434.00	8.30°	-58.60°	Non
Reflex	338.00	4.10°	-58.60°	Non	Reflex	437.00	7.40°	-58.70°	Non
Reflex	341.00	4.60°	-58.60°	Non	Reflex	440.00	9.00°	-58.60°	Oui
Reflex	344.00	4.30°	-58.60°	Non	Reflex	443.00	8.50°	-58.60°	Non
Reflex	347.00	4.90°	-58.60°	Non	Reflex	446.00	8.20°	-58.60°	Non
Reflex	350.00	4.30°	-58.60°	Non	Reflex	449.00	10.00°	-58.60°	Non
Reflex	353.00	4.20°	-58.60°	Non	Reflex	452.00	9.10°	-58.60°	Non
Reflex	356.00	4.50°	-58.70°	Non	Reflex	455.00	8.60°	-58.60°	Non
Reflex	359.00	3.90°	-58.70°	Non	Reflex	458.00	9.20°	-58.60°	Non
Reflex	362.00	5.30°	-58.70°	Non	Reflex	461.00	9.90°	-58.60°	Non
Reflex	365.00	5.30°	-58.70°	Non	Reflex	464.00	10.80°	-58.60°	Non
Reflex	368.00	4.80°	-58.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.80	MT <b>Mort-terrain</b> MT						
2.80	15.20	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique mauve à verdâtre.	2.80	4.00	D010474	1.20	0.418	0.418
			4.00	5.50	D010476	1.50	0.455	0.455
			5.50	7.00	D010477	1.50	2.560	2.560
			7.00	8.00	D010478	1.00	1.760	1.760
			8.00	9.50	D010479	1.50	0.018	0.018
			9.50	11.00	D010480	1.50	0.061	0.061
			11.00	12.50	D010481	1.50	0.031	0.031
			12.50	14.00	D010482	1.50	0.388	0.388
			14.00	15.20	D010483	1.20	0.685	0.685
15.20	24.30	RY <b>Brèche intrusive</b> Brèche intrusive silicifié, probablement une rhyolite bréchifiée?	15.20	16.90	D010484	1.70	1.295	1.295
			16.90	18.50	D010486	1.60	0.643	0.643
			18.50	20.00	D010487	1.50	3.100	3.100
			20.00	21.50	D010488	1.50	6.950	6.815
			21.50	23.00	D010489	1.50	0.343	0.343
			23.00	24.30	D010490	1.30	2.630	2.630
24.30	50.70	SY <b>Syénite</b> Syénite carbonatée, localement séricitisée	24.30	26.00	D010491	1.70	0.094	0.094
			26.00	27.50	D010492	1.50	0.051	0.051
			27.50	29.00	D010493	1.50	0.264	0.264
			29.00	30.50	D010494	1.50	0.256	0.256
			30.50	32.00	D010496	1.50	0.437	0.437
			32.00	33.50	D010497	1.50	1.070	1.070
			33.50	35.00	D010498	1.50	1.680	1.680
			35.00	36.50	D010499	1.50	0.509	0.509
			36.50	38.00	D010500	1.50	0.013	0.013
			38.00	39.50	D010501	1.50	0.022	0.022
			39.50	41.00	D010502	1.50	0.020	0.020
			41.00	42.50	D010503	1.50	0.021	0.021
			42.50	44.00	D010504	1.50	<0.005	0.001
			44.00	45.50	D010506	1.50	<0.005	0.001
			45.50	47.00	D010507	1.50	<0.005	0.001
			47.00	48.50	D010508	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
50.70	69.70	BA <b>Basalte 50°</b> Basalte silicifié et bréchique de 50.7 à 61.0 m et séricitisé, épidotisé et cisailé jusqu'à 69.6 m	48.50	49.50	D010509	1.00	<0.005		0.001
			49.50	50.70	D010510	1.20	<0.005		0.001
			50.70	52.50	D010511	1.80	0.009		0.009
			52.50	54.00	D010512	1.50	<0.005		0.001
			54.00	55.50	D010513	1.50	<0.005		0.001
			55.50	57.00	D010514	1.50	0.029		0.029
			57.00	58.00	D010516	1.00	0.006		0.006
			58.00	59.50	D010517	1.50	0.013		0.013
			59.50	61.00	D010518	1.50	0.006		0.006
50.70	61.00	BA; BRC <b>Basalte; Brèche de coulée</b> Silicifié et bréchifié.							
61.00	69.30	BA; CIS <b>Basalte; Cisailé</b> Séricitisé et cisailé à 45-30° du CA.	61.00	62.50	D010519	1.50	<0.005		0.001
			62.50	64.00	D010520	1.50	<0.005		0.001
			64.00	65.50	D010521	1.50	0.008		0.008
			65.50	67.00	D010522	1.50	0.005		0.005
			67.00	68.50	D010523	1.50	<0.005		0.001
			68.50	69.60	D010524	1.10	<0.005		0.001
			69.60	71.30	D010526	1.70	0.063		0.063
69.70	80.00	BA; BRC <b>Basalte; Brèche de coulée</b> Basalte bréchifié.	71.30	73.00	D010527	1.70	0.322		0.322
			73.00	74.00	D010528	1.00	0.056		0.056
			74.00	75.50	D010529	1.50	1.620		1.620
			75.50	77.00	D010530	1.50	0.013		0.013
			77.00	78.50	D010531	1.50	0.216		0.216
			78.50	80.00	D010532	1.50	0.093		0.093
80.00	105.50	PT <b>Porphyre trachytique 45°</b> Localement carbonaté, lates de plagio parallèle au CA parfois à 30°.	80.00	81.50	D010533	1.50	0.257		0.257
			81.50	83.00	D010534	1.50	0.009		0.009
			83.00	84.50	D010536	1.50	0.013		0.013
			84.50	86.00	D010537	1.50	0.070		0.070
			86.00	87.50	D010538	1.50	0.029		0.029
			87.50	89.00	D010539	1.50	0.011		0.011
			89.00	90.50	D010540	1.50	0.006		0.006
			90.50	92.00	D010541	1.50	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
105.50	203.00	BA <b>Basalte</b> Carbonaté, localement amygdulaire, silicifié et bréchifié par endroit.	92.00	93.50	D010542	1.50	0.027		0.027
			93.50	95.00	D010543	1.50	0.058		0.058
			95.00	96.50	D010544	1.50	0.005		0.005
			96.50	98.00	D010546	1.50	0.017		0.017
			98.00	99.50	D010547	1.50	0.021		0.021
			99.50	101.00	D010548	1.50	<0.005		0.001
			101.00	102.00	D010549	1.00	0.005		0.005
			102.00	103.50	D010550	1.50	0.007		0.007
			103.50	104.50	D010551	1.00	0.007		0.007
			104.50	106.00	D010552	1.50	0.409		0.409
			106.00	107.50	D010553	1.50	0.693		0.693
			107.50	109.00	D010554	1.50	0.267		0.267
			109.00	110.50	D010556	1.50	1.040		1.040
			110.50	112.00	D010557	1.50	0.039		0.039
			112.00	113.50	D010558	1.50	0.012		0.012
			113.50	118.90	SY <b>Syénite</b> Séricitisée, localement silicifiée et sub-bréchique.	113.50	115.00	D010559	1.50
115.00	116.50	D010560				1.50	<0.005		0.001
116.50	117.90	D010561				1.40	<0.005		0.001
117.90	118.90	D010562				1.00	0.835		0.835
118.90	120.50	D010563				1.60	0.521		0.521
120.50	122.00	D010564				1.50	3.190	3.29	3.290
122.00	123.50	D010566				1.50	2.790		2.790
123.50	125.00	D010567				1.50	0.185		0.185
125.00	126.50	D010568				1.50	5.740	5.83	5.830
126.50	128.10	D010569				1.60	0.859		0.859
129.80	137.00	BA <b>Basalte</b> Basalte silicifié, localement sub-bréchique.	128.10	129.80	D010570	1.70	0.127		0.127
			129.80	130.80	D010571	1.00	0.253		0.253
			130.80	131.60	D010572	0.80	0.005		0.005
			131.60	132.90	D010573	1.30	1.505		1.505
			132.90	134.30	D010574	1.40	10.000	12.85	12.850
			134.30	136.00	D010576	1.70	3.170	2.73	2.285
			136.00	137.00	D010577	1.00	0.100		0.100
			137.00	138.50	D010578	1.50	0.047		0.047

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	138.50	140.00	D010579	1.50	0.011		0.011
	140.00	141.50	D010580	1.50	0.005		0.005
	141.50	143.00	D010581	1.50	<0.005		0.001
	143.00	144.50	D010582	1.50	0.005		0.005
	144.50	146.00	D010583	1.50	<0.005		0.001
	146.00	147.50	D010584	1.50	<0.005		0.001
	147.50	149.00	D010586	1.50	<0.005		0.001
	149.00	150.50	D010587	1.50	0.005		0.005
	150.50	152.00	D010588	1.50	<0.005		0.001
	152.00	153.50	D010589	1.50	0.009		0.009
	153.50	155.00	D010590	1.50	<0.005		0.001
	155.00	156.50	D010591	1.50	0.005		0.005
	156.50	158.00	D010592	1.50	<0.005		0.001
	158.00	159.50	D010593	1.50	<0.005		0.001
	159.50	161.00	D010594	1.50	<0.005		0.001
	161.00	162.50	D010596	1.50	<0.005		0.001
	162.50	164.00	D010597	1.50	0.039		0.039
	164.00	165.50	D010598	1.50	0.020		0.020
	165.50	167.00	D010599	1.50	0.164		0.164
	167.00	168.50	D010600	1.50	0.518		0.518
	168.50	170.00	D010601	1.50	0.202		0.202
	170.00	171.50	D010602	1.50	<0.005		0.001
	171.50	173.00	D010603	1.50	<0.005		0.001
	173.00	174.50	D010604	1.50	<0.005		0.001
	174.50	176.00	D010606	1.50	0.049		0.049
	176.00	177.50	D010607	1.50	0.168		0.168
	177.50	179.00	D010608	1.50	0.029		0.029
	179.00	180.50	D010609	1.50	0.005		0.005
	180.50	182.00	D010610	1.50	0.005		0.005
	182.00	183.50	D010611	1.50	<0.005		0.001
	183.50	185.00	D010612	1.50	<0.005		0.001
	185.00	186.50	D010613	1.50	<0.005		0.001
	186.50	188.00	D010614	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			188.00	189.50	D010616	1.50	<0.005		0.001
			189.50	191.00	D010617	1.50	<0.005		0.001
			191.00	192.50	D010618	1.50	<0.005		0.001
			192.50	194.00	D010619	1.50	<0.005		0.001
			194.00	195.50	D010620	1.50	<0.005		0.001
			195.50	197.00	D010621	1.50	<0.005		0.001
			197.00	198.50	D010622	1.50	0.043		0.043
			198.50	200.00	D010623	1.50	<0.005		0.001
			200.00	201.50	D010624	1.50	<0.005		0.001
			201.50	203.00	D010626	1.50	<0.005		0.001
203.00	209.80	SY; POR	203.00	204.50	D010627	1.50	0.008		0.008
		<b>Syénite; Porphyrique</b>	204.50	206.00	D010628	1.50	0.341		0.341
		Syénite porphyrique carbonatée et localement séricitisée	206.00	207.50	D010629	1.50	<0.005		0.001
			207.50	208.80	D010630	1.30	0.396		0.396
			208.80	209.80	D010631	1.00	0.050		0.050
209.80	214.40	AN	209.80	211.50	D010632	1.70	<0.005		0.001
		<b>Andésite 50°</b>	211.50	213.00	D010633	1.50	<0.005		0.001
		Dyke de basalte-andésitique.	213.00	214.40	D010634	1.40	<0.005		0.001
214.40	464.00	SY; POR	214.40	216.00	D010636	1.60	<0.005		0.001
		<b>Syénite; Porphyrique</b>	216.00	217.50	D010637	1.50	0.018		0.018
		Syénite porphyrique carbonatée et localement séricitisée avec phénocristaux de plagio fins à grossiers et parfois zonés.	217.50	219.00	D010638	1.50	0.014		0.014
			219.00	220.50	D010639	1.50	<0.005		0.001
			220.50	222.00	D010640	1.50	<0.005		0.001
			222.00	223.50	D010641	1.50	<0.005		0.001
			223.50	225.00	D010642	1.50	0.008		0.008
			225.00	226.50	D010643	1.50	0.034		0.034
			226.50	228.00	D010644	1.50	<0.005		0.001
			228.00	229.50	D010646	1.50	<0.005		0.001
			229.50	231.00	D010647	1.50	<0.005		0.001
			231.00	232.50	D010648	1.50	0.177		0.177
			232.50	234.00	D010649	1.50	0.023		0.023
			234.00	235.50	D010650	1.50	0.020		0.020
			235.50	237.00	D010651	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	237.00	238.50	D010652	1.50	<0.005		0.001
	238.50	240.00	D010653	1.50	0.029		0.029
	240.00	241.50	D010654	1.50	<0.005		0.001
	241.50	243.00	D010656	1.50	<0.005		0.001
	243.00	244.50	D010657	1.50	0.015		0.015
	244.50	246.00	D010658	1.50	0.042		0.042
	246.00	247.50	D010659	1.50	0.068		0.068
	247.50	249.00	D010660	1.50	<0.005		0.001
	249.00	250.50	D010661	1.50	<0.005		0.001
	250.50	252.00	D010662	1.50	0.036		0.036
	252.00	253.50	D010663	1.50	0.013		0.013
	253.50	255.00	D010664	1.50	0.012		0.012
	255.00	256.50	D010666	1.50	0.013		0.013
	256.50	258.00	D010667	1.50	0.007		0.007
	258.00	259.50	D010668	1.50	0.015		0.015
	259.50	261.00	D010669	1.50	0.052		0.052
	261.00	262.50	D010670	1.50	0.106		0.106
	262.50	264.00	D010671	1.50	0.039		0.039
	264.00	265.50	D010672	1.50	0.009		0.009
	265.50	267.00	D010673	1.50	0.009		0.009
	267.00	268.50	D010674	1.50	<0.005		0.001
	268.50	270.00	D010676	1.50	0.005		0.005
	270.00	271.50	D010677	1.50	0.005		0.005
	271.50	273.00	D010678	1.50	0.009		0.009
	273.00	274.50	D010679	1.50	0.006		0.006
	274.50	276.00	D010680	1.50	<0.005		0.001
	276.00	277.50	D010681	1.50	<0.005		0.001
	277.50	279.00	D010682	1.50	<0.005		0.001
	279.00	280.50	D010683	1.50	0.007		0.007
	280.50	282.00	D010684	1.50	0.108		0.108
	282.00	283.50	D010686	1.50	0.013		0.013
	283.50	285.00	D010687	1.50	0.029		0.029
	285.00	286.50	D010688	1.50	0.020		0.020

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	286.50	288.00	D010689	1.50	0.029		0.029
	288.00	289.50	D010690	1.50	0.024		0.024
	289.50	291.00	D010691	1.50	0.022		0.022
	291.00	292.50	D010692	1.50	0.012		0.012
	292.50	294.00	D010693	1.50	0.010		0.010
	294.00	295.50	D010694	1.50	<0.005		0.001
	295.50	297.00	D010696	1.50	<0.005		0.001
	297.00	298.50	D010697	1.50	<0.005		0.001
	298.50	300.00	D010698	1.50	0.024		0.024
	300.00	301.50	D010699	1.50	<0.005		0.001
	301.50	303.00	D010700	1.50	0.010		0.010
	303.00	304.50	D010701	1.50	0.021		0.021
	304.50	306.00	D010702	1.50	0.027		0.027
	306.00	307.50	D010703	1.50	0.018		0.018
	307.50	309.00	D010704	1.50	0.015		0.015
	309.00	310.60	D010706	1.60	0.023		0.023
	310.60	312.00	D010707	1.40	0.011		0.011
	312.00	313.50	D010708	1.50	0.011		0.011
	313.50	315.00	D010709	1.50	0.012		0.012
	315.00	316.50	D010710	1.50	0.086		0.086
	316.50	318.00	D010711	1.50	0.067		0.067
	318.00	319.50	D010712	1.50	<0.005		0.001
	319.50	321.00	D010713	1.50	0.005		0.005
	321.00	322.50	D010714	1.50	0.008		0.008
	322.50	324.00	D010716	1.50	0.013		0.013
	324.00	325.50	D010717	1.50	0.049		0.049
	325.50	327.00	D010718	1.50	0.058		0.058
	327.00	328.50	D010719	1.50	0.043		0.043
	328.50	330.00	D010720	1.50	1.480		1.480
	330.00	331.50	D010721	1.50	0.125		0.125
	331.50	333.00	D010722	1.50	1.215		1.215
	333.00	334.50	D010723	1.50	0.305		0.305
	334.50	336.00	D010724	1.50	0.320		0.320

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	336.00	337.50	D010726	1.50	0.317		0.317
	337.50	339.00	D010727	1.50	0.103		0.103
	339.00	340.50	D010728	1.50	0.129		0.129
	340.50	342.00	D010729	1.50	0.043		0.043
	342.00	343.50	D010730	1.50	0.045		0.045
	343.50	345.00	D010731	1.50	0.029		0.029
	345.00	346.50	D010732	1.50	0.117		0.117
	346.50	348.00	D010733	1.50	0.167		0.167
	348.00	349.50	D010734	1.50	0.119		0.119
	349.50	351.00	D010736	1.50	0.027		0.027
	351.00	352.50	D010737	1.50	0.150		0.150
	352.50	354.00	D010738	1.50	0.911		0.911
	354.00	355.50	D010739	1.50	0.613		0.613
	355.50	357.00	D010740	1.50	0.069		0.069
	357.00	358.50	D010741	1.50	0.092		0.092
	358.50	360.00	D010742	1.50	0.058		0.058
	360.00	361.50	D010743	1.50	0.005		0.005
	361.50	363.00	D010744	1.50	<0.005		0.001
	363.00	364.50	D010746	1.50	0.008		0.008
	364.50	366.00	D010747	1.50	0.116		0.116
	366.00	367.50	D010748	1.50	0.015		0.015
	367.50	369.00	D010749	1.50	0.014		0.014
	369.00	370.50	D010750	1.50	0.019		0.019
	370.50	372.00	D010751	1.50	0.013		0.013
	372.00	373.50	D010752	1.50	0.107		0.107
	373.50	375.00	D010753	1.50	0.058		0.058
	375.00	376.50	D010754	1.50	0.247		0.247
	376.50	378.00	D010756	1.50	0.408		0.408
	378.00	379.50	D010757	1.50	0.698		0.698
	379.50	381.00	D010758	1.50	0.350		0.350
	381.00	382.50	D010759	1.50	0.727		0.727
	382.50	384.00	D010760	1.50	0.182		0.182
	384.00	385.50	D010761	1.50	0.067		0.067

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
397.50	403.00	SY; CAT <b>Syénite 30°; Cataclasée</b> Brèche de syénite fortement carbonatée, séricitisée, fragments d'ordre mm à cm.	385.50	387.00	D010762	1.50	0.127		0.127
			387.00	388.50	D010763	1.50	<0.005		0.001
			388.50	390.00	D010764	1.50	0.021		0.021
			390.00	391.50	D010766	1.50	0.514		0.514
			391.50	393.00	D010767	1.50	0.397		0.397
			393.00	394.50	D010768	1.50	0.029		0.029
			394.50	396.00	D010769	1.50	0.025		0.025
			396.00	397.50	D010770	1.50	0.043		0.043
			397.50	399.00	D010771	1.50	1.930		1.930
			399.00	400.50	D010772	1.50	0.436		0.436
			400.50	402.00	D010773	1.50	0.460		0.460
			402.00	403.00	D010774	1.00	1.185		1.185
			403.00	404.50	D010776	1.50	0.543		0.543
			404.50	406.00	D010777	1.50	0.114		0.114
			406.00	407.50	D010778	1.50	0.671		0.671
			407.50	409.00	D010779	1.50	0.910		0.910
			409.00	410.50	D010780	1.50	0.707		0.707
			410.50	412.00	D010781	1.50	0.712		0.712
			412.00	413.00	D010782	1.00	0.340		0.340
			413.00	414.60	D010783	1.60	0.874		0.874
			414.60	416.00	D010784	1.40	0.215		0.215
			416.00	417.50	D010786	1.50	0.102		0.102
			417.50	419.00	D010787	1.50	0.513		0.513
			419.00	420.50	D010788	1.50	0.610		0.610
			420.50	422.00	D010789	1.50	0.562		0.562
			422.00	423.50	D010790	1.50	0.189		0.189
423.50	425.00	D010791	1.50	0.954		0.954			
425.00	426.50	D010792	1.50	0.471		0.471			
426.50	428.00	D010793	1.50	0.520		0.520			
428.00	429.70	D010794	1.70	0.796		0.796			
429.70	431.40	D010796	1.70	0.910		0.910			
431.40	433.00	D010797	1.60	<0.005		0.001			
433.00	434.50	D010798	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	434.50	436.00	D010799	1.50	<0.005		0.001
	436.00	437.50	D010800	1.50	0.028		0.028
	437.50	439.00	D010801	1.50	<0.005		0.001
	439.00	440.50	D010802	1.50	0.009		0.009
	440.50	442.00	D010803	1.50	<0.005		0.001
	442.00	443.50	D010804	1.50	<0.005		0.001
	443.50	445.00	D010806	1.50	0.035		0.035
	445.00	446.50	D010807	1.50	0.078		0.078
	446.50	448.00	D010808	1.50	<0.005		0.001
	448.00	449.50	D010809	1.50	<0.005		0.001
	449.50	451.00	D010810	1.50	<0.005		0.001
	451.00	452.50	D010811	1.50	<0.005		0.001
	452.50	454.00	D010812	1.50	<0.005		0.001
	454.00	455.50	D010813	1.50	0.068		0.068
	455.50	457.00	D010814	1.50	0.124		0.124
	457.00	458.50	D010816	1.50	0.016		0.016
	458.50	460.00	D010817	1.50	0.005		0.005
	460.00	461.50	D010818	1.50	<0.005		0.001
	461.50	463.00	D010819	1.50	<0.005		0.001
	463.00	464.00	D010820	1.00	<0.005		0.001
464.00	Fin du sondage Nombre d'échantillons : 312 Nombre d'échantillons QAQC : 35 Longueur totale échantillonnée : 461.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
2.80	4.00	D010475	D010474	1.20	0.424	0.424
15.20	16.90	D010485	G2	1.70	4.060	4.040
29.00	30.50	D010495	D010494	1.50	0.399	0.399
42.50	44.00	D010505	M1	1.50	<0.005	0.001
57.00	58.00	D010515	D010514	1.00	0.026	0.026
68.50	69.60	D010525	C4	1.10	1.345	1.345
81.50	83.00	D010535	D010534	1.50	0.008	0.008
95.00	96.50	D010545	M1	1.50	<0.005	0.001
107.50	109.00	D010555	D010554	1.50	0.153	0.153
120.50	122.00	D010565	D2	1.50	0.827	0.827
134.30	136.00	D010575	D010574	1.70	10.000	11.550
146.00	147.50	D010585	M1	1.50	<0.005	0.001
161.00	162.50	D010595	D010594	1.50	<0.005	0.001
173.00	174.50	D010605	F2	1.50	8.240	8.190
186.50	188.00	D010615	D010614	1.50	<0.005	0.001
200.00	200.00	D010625	M1	0.00	<0.005	0.001
213.00	213.00	D010635	D010634	0.00	<0.005	0.001
226.50	226.50	D010645	G2	0.00	2.850	2.850
240.00	241.50	D010655	D010654	1.50	<0.005	0.001
253.50	253.50	D010665	M1	0.00	<0.005	0.001
267.00	268.50	D010675	D010674	1.50	0.007	0.007
280.50	280.50	D010685	H	0.00	0.906	0.906
294.00	295.50	D010695	D010694	1.50	<0.005	0.001
307.50	307.50	D010705	A3	0.00	0.602	0.602
321.00	322.50	D010715	D010714	1.50	0.007	0.007
334.50	336.50	D010725	M1	2.00	<0.005	0.001
348.00	349.50	D010735	D010734	1.50	0.111	0.111
361.50	361.50	D010745	B4	0.00	2.280	2.280
375.00	376.50	D010755	D010754	1.50	0.244	0.244
388.50	388.50	D010765	M1	0.00	<0.005	0.001
402.00	403.00	D010775	D010774	1.00	1.220	1.220
414.60	414.60	D010785	C4	0.00	1.260	1.260
428.00	429.70	D010795	D010794	1.70	0.808	0.808

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
442.00	442.00	D010805	M1	0.00	<0.005	0.001
455.50	457.00	D010815	D010814	1.50	0.018	0.018

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-132**

Titre minier :

Section :                      631300

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy gbaguidi

Lot :

Du :                              2010-03-22

Date de description :

Au :                             2010-03-28

Collet

UTM

Azimut :                      0.00°  
 Plongée :                    -68.00°  
 Longueur :                458.00 m

Est	631 299.7
Nord	5 374 200.2
Élévation	299.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	11.00	15.40°	-68.10°	Oui
Reflex	14.00	3.70°	-68.10°	Non
Reflex	17.00	3.90°	-68.10°	Non
Reflex	20.00	3.70°	-68.00°	Non
Reflex	23.00	3.60°	-68.00°	Non
Reflex	26.00	3.80°	-68.10°	Non
Reflex	29.00	4.50°	-68.60°	Non
Reflex	32.00	4.20°	-67.90°	Non
Reflex	35.00	4.20°	-67.90°	Non
Reflex	38.00	4.30°	-67.70°	Non
Reflex	41.00	4.70°	-68.00°	Non
Reflex	44.00	4.60°	-67.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	47.00	5.00°	-67.90°	Non
Reflex	50.00	4.90°	-67.90°	Non
Reflex	53.00	5.00°	-67.90°	Non
Reflex	56.00	5.00°	-67.90°	Non
Reflex	59.00	5.10°	-67.90°	Non
Reflex	62.00	5.10°	-67.90°	Non
Reflex	65.00	5.10°	-67.90°	Non
Reflex	68.00	5.30°	-67.90°	Non
Reflex	71.00	5.30°	-67.80°	Non
Reflex	74.00	5.40°	-67.80°	Non
Reflex	77.00	5.30°	-67.80°	Non
Reflex	80.00	5.30°	-67.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	83.00	5.40°	-67.70°	Non
Reflex	86.00	5.00°	-67.40°	Non
Reflex	89.00	6.00°	-67.10°	Non
Reflex	92.00	5.80°	-67.70°	Non
Reflex	95.00	5.90°	-67.70°	Non
Reflex	98.00	5.70°	-67.40°	Non
Reflex	101.00	6.10°	-67.80°	Non
Reflex	104.00	6.20°	-67.80°	Non
Reflex	107.00	6.30°	-67.80°	Non
Reflex	110.00	6.40°	-67.80°	Non
Reflex	113.00	6.50°	-67.80°	Non
Reflex	116.00	6.50°	-67.80°	Non
Reflex	119.00	6.60°	-67.80°	Non
Reflex	122.00	6.60°	-67.70°	Non
Reflex	125.00	6.80°	-67.80°	Non
Reflex	128.00	6.90°	-67.80°	Non
Reflex	131.00	6.80°	-67.60°	Non
Reflex	134.00	6.90°	-67.70°	Non
Reflex	137.00	6.90°	-67.70°	Non
Reflex	140.00	6.80°	-67.70°	Non
Reflex	143.00	6.80°	-67.70°	Non
Reflex	146.00	6.80°	-67.80°	Non
Reflex	149.00	6.90°	-67.70°	Non
Reflex	152.00	6.70°	-67.70°	Non
Reflex	155.00	5.70°	-67.00°	Non
Reflex	158.00	7.00°	-67.90°	Non
Reflex	161.00	3.70°	-67.60°	Oui
Reflex	164.00	10.30°	-67.60°	Oui
Reflex	167.00	8.00°	-67.60°	Non
Reflex	170.00	8.30°	-67.50°	Non
Reflex	173.00	8.60°	-67.50°	Non
Reflex	176.00	7.90°	-67.50°	Non
Reflex	179.00	8.70°	-67.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	182.00	8.60°	-67.40°	Non
Reflex	185.00	8.70°	-67.40°	Non
Reflex	188.00	8.80°	-67.40°	Non
Reflex	191.00	8.50°	-67.40°	Non
Reflex	194.00	6.40°	-67.30°	Oui
Reflex	197.00	10.30°	-67.20°	Oui
Reflex	200.00	9.60°	-67.20°	Non
Reflex	203.00	9.20°	-67.20°	Non
Reflex	206.00	8.80°	-67.20°	Non
Reflex	209.00	9.00°	-67.20°	Non
Reflex	212.00	8.90°	-67.10°	Non
Reflex	215.00	8.90°	-67.00°	Non
Reflex	218.00	8.90°	-67.00°	Non
Reflex	221.00	8.90°	-67.00°	Non
Reflex	224.00	8.80°	-67.00°	Non
Reflex	227.00	9.70°	-66.90°	Non
Reflex	230.00	9.80°	-66.90°	Non
Reflex	233.00	22.40°	-66.90°	Oui
Reflex	236.00	8.30°	-66.80°	Non
Reflex	239.00	10.80°	-66.80°	Non
Reflex	242.00	5.70°	-66.70°	Non
Reflex	245.00	6.20°	-66.70°	Non
Reflex	248.00	7.80°	-66.70°	Non
Reflex	251.00	6.10°	-66.60°	Non
Reflex	254.00	9.00°	-66.60°	Non
Reflex	257.00	10.40°	-66.60°	Non
Reflex	260.00	9.10°	-66.60°	Non
Reflex	263.00	9.90°	-66.70°	Non
Reflex	266.00	10.00°	-66.60°	Non
Reflex	269.00	9.70°	-66.70°	Non
Reflex	272.00	9.50°	-66.70°	Non
Reflex	275.00	9.60°	-66.70°	Non
Reflex	278.00	9.80°	-66.60°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	281.00	10.80°	-66.70°	Non	Reflex	380.00	11.20°	-66.40°	Non
Reflex	284.00	11.00°	-66.70°	Non	Reflex	383.00	11.10°	-66.50°	Non
Reflex	287.00	10.60°	-66.70°	Non	Reflex	386.00	12.30°	-66.40°	Non
Reflex	290.00	10.40°	-66.60°	Non	Reflex	389.00	12.50°	-66.40°	Non
Reflex	293.00	10.20°	-66.60°	Non	Reflex	392.00	11.80°	-66.40°	Non
Reflex	296.00	11.50°	-66.60°	Non	Reflex	395.00	11.70°	-66.40°	Non
Reflex	299.00	10.30°	-66.60°	Non	Reflex	398.00	12.00°	-66.50°	Non
Reflex	302.00	10.20°	-66.60°	Non	Reflex	401.00	12.00°	-66.50°	Non
Reflex	305.00	10.30°	-66.60°	Non	Reflex	404.00	12.10°	-66.50°	Non
Reflex	308.00	10.40°	-66.60°	Non	Reflex	407.00	12.30°	-66.50°	Non
Reflex	311.00	10.60°	-66.60°	Non	Reflex	410.00	12.00°	-66.40°	Non
Reflex	314.00	10.50°	-66.60°	Non	Reflex	413.00	11.90°	-66.40°	Non
Reflex	317.00	10.40°	-66.60°	Non	Reflex	416.00	12.20°	-66.40°	Non
Reflex	320.00	10.30°	-66.60°	Non	Reflex	419.00	12.40°	-66.40°	Non
Reflex	323.00	10.70°	-66.60°	Non	Reflex	422.00	12.30°	-66.40°	Non
Reflex	326.00	10.60°	-66.60°	Non	Reflex	425.00	12.30°	-66.40°	Non
Reflex	329.00	11.80°	-66.60°	Non	Reflex	428.00	12.30°	-66.50°	Non
Reflex	332.00	10.70°	-66.50°	Non	Reflex	431.00	12.40°	-66.50°	Non
Reflex	335.00	11.10°	-66.50°	Non	Reflex	434.00	12.50°	-66.40°	Non
Reflex	338.00	10.20°	-66.50°	Non	Reflex	437.00	12.70°	-66.50°	Non
Reflex	341.00	10.30°	-66.40°	Non	Reflex	440.00	12.70°	-66.40°	Non
Reflex	344.00	10.30°	-66.40°	Non	Reflex	443.00	12.70°	-66.40°	Non
Reflex	347.00	11.70°	-66.40°	Oui	Reflex	446.00	12.70°	-66.40°	Non
Reflex	350.00	10.80°	-66.40°	Non	Reflex	449.00	13.10°	-66.40°	Non
Reflex	353.00	11.10°	-66.40°	Non	Reflex	452.00	12.50°	-66.40°	Non
Reflex	356.00	10.90°	-66.40°	Non	Reflex	455.00	333.70°	-69.00°	Oui
Reflex	359.00	11.00°	-66.40°	Non	Reflex	458.00	314.60°	-82.70°	Oui
Reflex	362.00	11.30°	-66.40°	Non					
Reflex	365.00	11.00°	-66.40°	Non					
Reflex	368.00	10.90°	-66.40°	Non					
Reflex	371.00	10.90°	-66.40°	Non					
Reflex	374.00	11.00°	-66.50°	Non					
Reflex	377.00	11.00°	-66.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.70	MT <b>Mort-terrain</b>						
3.70	15.80	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique séricitisée	3.70	5.00	D011245	1.30		0.129
			5.00	6.50	D011246	1.50		0.439
			6.50	8.00	D011247	1.50		1.250
			8.00	9.50	D011248	1.50		0.062
			9.50	11.00	D011249	1.50		0.043
			11.00	12.50	D011250	1.50		0.006
			12.50	14.10	D011251	1.60		0.360
			14.10	15.80	D011252	1.70		0.069
15.80	27.90	SY; BR <b>Syénite; Bréchifié</b> Syénite bréchifiée, faiblement hématisée et séricitisée.	15.80	17.50	D011253	1.70		0.166
			17.50	19.00	D011254	1.50		1.045
			19.00	20.40	D011256	1.40		0.509
			20.40	22.00	D011257	1.60		1.675
			22.00	23.00	D011258	1.00	11.45	11.450
			23.00	24.50	D011259	1.50		2.660
			24.50	26.20	D011260	1.70		1.235
			26.20	27.90	D011261	1.70		2.390
27.90	58.00	SY; POR <b>Syénite; Porphyrique</b> Localement bréchifiée, faiblement hématisée et épidotisée.	27.90	29.50	D011262	1.60		0.050
			29.50	31.00	D011263	1.50		0.780
			31.00	32.50	D011264	1.50		0.183
			32.50	34.00	D011266	1.50		0.812
			34.00	35.50	D011267	1.50		1.615
			35.50	37.00	D011268	1.50	4.44	4.440
			37.00	38.50	D011269	1.50		1.155
			38.50	40.00	D011270	1.50		1.200
			40.00	41.50	D011271	1.50		0.422
			41.50	43.00	D011272	1.50		0.013
			43.00	44.50	D011273	1.50		0.016
			44.50	46.00	D011274	1.50		0.025
			46.00	47.50	D011276	1.50		0.182
			47.50	49.00	D011277	1.50		<0.005
			49.00	50.50	D011278	1.50		<0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
58.00	125.60	BA <b>Basalte</b> Localement bréchifié et silicifié, chloritisé, par endroit hématisé.	50.50	52.00	D011279	1.50	<0.005		0.001
			52.00	53.00	D011280	1.00	<0.005		0.001
			53.00	54.30	D011281	1.30	0.005		0.005
			54.30	55.30	D011282	1.00	0.005		0.005
			55.30	56.30	D011283	1.00	<0.005		0.001
			56.30	58.00	D011284	1.70	<0.005		0.001
			58.00	59.50	D011286	1.50	0.005		0.005
			59.50	61.00	D011287	1.50	<0.005		0.001
			61.00	62.50	D011288	1.50	<0.005		0.001
			62.50	64.00	D011289	1.50	<0.005		0.001
			64.00	65.30	D011290	1.30	0.006		0.006
			65.30	66.60	D011291	1.30	0.005		0.005
			66.60	68.30	D011292	1.70	<0.005		0.001
			68.30	70.00	D011293	1.70	<0.005		0.001
			70.00	71.50	D011294	1.50	0.005		0.005
			71.50	73.00	D011296	1.50	0.028		0.028
			73.00	74.50	D011297	1.50	<0.005		0.001
			74.50	76.00	D011298	1.50	<0.005		0.001
			76.00	77.50	D011299	1.50	0.009		0.009
			77.50	79.00	D011300	1.50	<0.005		0.001
			79.00	80.50	D011301	1.50	<0.005		0.001
			80.50	82.00	D011302	1.50	0.049		0.049
			82.00	83.50	D011303	1.50	0.466		0.466
			83.50	85.00	D011304	1.50	0.105		0.105
			85.00	86.50	D011306	1.50	0.095		0.095
			86.50	88.00	D011307	1.50	2.050		2.050
			88.00	89.50	D011308	1.50	0.221		0.221
89.50	91.00	D011309	1.50	0.045		0.045			
91.00	92.50	D011310	1.50	0.083		0.083			
92.50	94.00	D011311	1.50	0.120		0.120			
94.00	95.50	D011312	1.50	0.106		0.106			
95.50	97.00	D011313	1.50	0.200		0.200			
97.00	98.50	D011314	1.50	0.131		0.131			

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
125.60	134.00	PT; SY  <b>Porphyre trachytique 45°; Syénite</b> Syénite trachitique, lates de plagio mm à cm, orienté à 0-90°, hématisé et séricitisé, localement silicifié.	98.50	100.00	D011316	1.50	0.124		0.124			
			100.00	101.50	D011317	1.50	0.912		0.912			
			101.50	103.00	D011318	1.50	0.106		0.106			
			103.00	104.50	D011319	1.50	0.040		0.040			
			104.50	106.00	D011320	1.50	0.035		0.035			
			106.00	107.60	D011321	1.60	0.015		0.015			
			107.60	109.00	D011322	1.40	0.007		0.007			
			109.00	110.50	D011323	1.50	0.005		0.005			
			110.50	112.00	D011324	1.50	<0.005		0.001			
			112.00	113.50	D011326	1.50	<0.005		0.001			
			113.50	115.00	D011327	1.50	<0.005		0.001			
			115.00	116.50	D011328	1.50	<0.005		0.001			
			116.50	118.00	D011329	1.50	<0.005		0.001			
			118.00	119.50	D011330	1.50	0.005		0.005			
			119.50	121.00	D011331	1.50	0.010		0.010			
			121.00	122.50	D011332	1.50	0.006		0.006			
			122.50	124.00	D011333	1.50	<0.005		0.001			
			124.00	125.60	D011334	1.60	<0.005		0.001			
			134.00	221.40	BA; AMY  <b>Basalte 40°; Amygdalaire</b> Localement silicifié et bréchifié, amygdules mm à pluri cm, magnétique au contact inf avec syénite.	125.60	127.00	D011336	1.40	0.026		0.026
						127.00	128.50	D011337	1.50	0.094		0.094
128.50	130.00	D011338				1.50	0.168		0.168			
130.00	131.50	D011339				1.50	0.333		0.333			
131.50	133.00	D011340				1.50	0.647		0.647			
133.00	134.00	D011341				1.00	2.170		2.170			
134.00	135.50	D011342				1.50	0.553		0.553			
135.50	137.00	D011343				1.50	0.014		0.014			
137.00	138.00	D011344				1.00	0.220		0.220			
138.00	139.50	D011346				1.50	0.013		0.013			
139.50	141.00	D011347				1.50	0.134		0.134			
141.00	142.00	D011348	1.00	0.009		0.009						
142.00	143.60	D011349	1.60	0.016		0.016						
143.60	145.00	D011350	1.40	0.165		0.165						
145.00	146.50	D011351	1.50	0.038		0.038						

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	146.50	148.00	D011352	1.50	0.853		0.853
	148.00	149.50	D011353	1.50	0.013		0.013
	149.50	151.00	D011354	1.50	1.315		1.315
	151.00	152.50	D011356	1.50	0.005		0.005
	152.50	154.00	D011357	1.50	0.071		0.071
	154.00	155.50	D011358	1.50	<0.005		0.001
	155.50	157.00	D011359	1.50	<0.005		0.001
	157.00	158.50	D011360	1.50	0.007		0.007
	158.50	160.00	D011361	1.50	<0.005		0.001
	160.00	161.50	D011362	1.50	0.005		0.005
	161.50	163.00	D011363	1.50	<0.005		0.001
	163.00	164.50	D011364	1.50	<0.005		0.001
	164.50	166.00	D011366	1.50	0.005		0.005
	166.00	167.50	D011367	1.50	<0.005		0.001
	167.50	169.00	D011368	1.50	0.005		0.005
	169.00	170.50	D011369	1.50	<0.005		0.001
	170.50	172.00	D011370	1.50	<0.005		0.001
	172.00	173.50	D011371	1.50	0.006		0.006
	173.50	175.00	D011372	1.50	<0.005		0.001
	175.00	176.50	D011373	1.50	<0.005		0.001
	176.50	178.00	D011374	1.50	<0.005		0.001
	178.00	179.50	D011376	1.50	0.005		0.005
	179.50	181.00	D011377	1.50	0.005		0.005
	181.00	182.50	D011378	1.50	0.005		0.005
	182.50	184.00	D011379	1.50	<0.005		0.001
	184.00	185.50	D011380	1.50	<0.005		0.001
	185.50	187.00	D011381	1.50	<0.005		0.001
	187.00	188.50	D011382	1.50	<0.005		0.001
	188.50	190.00	D011383	1.50	0.028		0.028
	190.00	191.00	D011384	1.00	<0.005		0.001
	191.00	192.00	D011386	1.00	<0.005		0.001
	192.00	193.50	D011387	1.50	0.442		0.442
	193.50	195.20	D011388	1.70	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			195.20	196.90	D011389	1.70	<0.005		0.001
			196.90	198.50	D011390	1.60	<0.005		0.001
			198.50	200.00	D011391	1.50	0.012		0.012
			200.00	201.00	D011392	1.00	<0.005		0.001
			201.00	202.50	D011393	1.50	1.475		1.475
			202.50	204.00	D011394	1.50	<0.005		0.001
			204.00	205.50	D011396	1.50	0.008		0.008
			205.50	207.00	D011397	1.50	<0.005		0.001
			207.00	208.50	D011398	1.50	<0.005		0.001
			208.50	210.00	D011399	1.50	<0.005		0.001
			210.00	211.50	D011400	1.50	<0.005		0.001
			211.50	213.00	D011401	1.50	<0.005		0.001
			213.00	214.50	D011402	1.50	<0.005		0.001
			214.50	216.00	D011403	1.50	0.129		0.129
			216.00	217.50	D011404	1.50	0.008		0.008
			217.50	219.00	D011406	1.50	0.008		0.008
			219.00	220.00	D011407	1.00	<0.005		0.001
			220.00	221.40	D011408	1.40	<0.005		0.001
221.40	226.80	SY; POR <b>Syénite 25°; Porphyrique</b> Porphyre syénitique hématisé, magnétique, séricitisé et carbonaté.	221.40	223.00	D011409	1.60	<0.005		0.001
			223.00	224.50	D011410	1.50	<0.005		0.001
			224.50	225.80	D011411	1.30	<0.005		0.001
			225.80	226.80	D011412	1.00	<0.005		0.001
226.80	237.10	BA; AMY <b>Basalte 30°; Amygdalaire</b> Basalte amygdalaire séricitisé, magnétique, chloritisé et carbonaté.	226.80	228.50	D011413	1.70	0.142		0.142
			228.50	230.00	D011414	1.50	<0.005		0.001
			230.00	231.50	D011416	1.50	<0.005		0.001
			231.50	233.00	D011417	1.50	0.005		0.005
			233.00	234.50	D011418	1.50	0.070		0.070
			234.50	236.00	D011419	1.50	0.762		0.762
			236.00	237.10	D011420	1.10	<0.005		0.001
237.10	238.40	SY; POR <b>Syénite 45°; Porphyrique</b> Syénite porphyrique carbonatée, magnétique et séricitisée.	237.10	238.40	D011421	1.30	<0.005		0.001
238.40	245.30	BA; MAS <b>Basalte 50°; Roche massive</b>	238.40	240.00	D011422	1.60	<0.005		0.001
			240.00	241.50	D011423	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
245.30	458.00	SY; POR <b>Syénite 20°; Porphyrique</b> Syénite porphyrique carbonatée, magnétique et faiblement séricitisée.	241.50	243.00	D011424	1.50	<0.005		0.001
			243.00	244.00	D011426	1.00	<0.005		0.001
			244.00	245.30	D011427	1.30	<0.005		0.001
			245.30	246.30	D011428	1.00	0.687		0.687
			246.30	248.00	D011429	1.70	0.006		0.006
			248.00	249.50	D011430	1.50	<0.005		0.001
			249.50	251.00	D011431	1.50	<0.005		0.001
			251.00	252.50	D011432	1.50	<0.005		0.001
			252.50	254.00	D011433	1.50	<0.005		0.001
			254.00	255.50	D011434	1.50	0.005		0.005
			255.50	257.00	D011436	1.50	<0.005		0.001
			257.00	258.50	D011437	1.50	0.006		0.006
			258.50	260.00	D011438	1.50	0.024		0.024
			260.00	261.50	D011439	1.50	0.014		0.014
			261.50	263.00	D011440	1.50	<0.005		0.001
			263.00	264.50	D011441	1.50	0.329		0.329
			264.50	266.00	D011442	1.50	0.161		0.161
			266.00	267.50	D011443	1.50	0.019		0.019
			267.50	269.00	D011444	1.50	0.018		0.018
			269.00	270.50	D011446	1.50	<0.005		0.001
			270.50	272.00	D011447	1.50	0.067		0.067
			272.00	273.50	D011448	1.50	0.030		0.030
			273.50	275.00	D011449	1.50	0.007		0.007
			275.00	276.50	D011450	1.50	0.005		0.005
			276.50	278.00	D011451	1.50	0.009		0.009
			278.00	279.50	D011452	1.50	<0.005		0.001
			279.50	281.00	D011453	1.50	0.013		0.013
			281.00	282.50	D011454	1.50	<0.005		0.001
282.50	284.00	D011456	1.50	<0.005		0.001			
284.00	285.50	D011457	1.50	0.017		0.017			
285.50	287.00	D011458	1.50	0.048		0.048			
287.00	288.50	D011459	1.50	0.017		0.017			
288.50	290.00	D011460	1.50	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	290.00	291.50	D011461	1.50	0.023		0.023
	291.50	293.00	D011462	1.50	0.041		0.041
	293.00	294.50	D011463	1.50	0.039		0.039
	294.50	296.00	D011464	1.50	0.432		0.432
	296.00	297.50	D011466	1.50	<0.005		0.001
	297.50	299.00	D011467	1.50	0.043		0.043
	299.00	300.50	D011468	1.50	0.112		0.112
	300.50	302.00	D011469	1.50	1.015		1.015
	302.00	303.50	D011470	1.50	0.055		0.055
	303.50	305.00	D011471	1.50	0.013		0.013
	305.00	306.50	D011472	1.50	0.014		0.014
	306.50	308.00	D011473	1.50	0.034		0.034
	308.00	309.50	D011474	1.50	0.009		0.009
	309.50	311.00	D011476	1.50	0.165		0.165
	311.00	312.50	D011477	1.50	0.192		0.192
	312.50	314.00	D011478	1.50	0.006		0.006
	314.00	315.50	D011479	1.50	<0.005		0.001
	315.50	317.00	D011480	1.50	0.005		0.005
	317.00	318.50	D011481	1.50	0.005		0.005
	318.50	320.00	D011482	1.50	0.009		0.009
	320.00	321.50	D011483	1.50	<0.005		0.001
	321.50	323.00	D011484	1.50	0.007		0.007
	323.00	324.50	D011486	1.50	0.005		0.005
	324.50	326.00	D011487	1.50	0.007		0.007
	326.00	327.50	D011488	1.50	0.027		0.027
	327.50	329.00	D011489	1.50	<0.005		0.001
	329.00	330.50	D011490	1.50	<0.005		0.001
	330.50	332.00	D011491	1.50	<0.005		0.001
	332.00	333.50	D011492	1.50	<0.005		0.001
	333.50	335.00	D011493	1.50	0.006		0.006
	335.00	336.50	D011494	1.50	0.010		0.010
	336.50	338.00	D011496	1.50	<0.005		0.001
	338.00	339.50	D011497	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	339.50	341.00	D011498	1.50	<0.005		0.001
	341.00	342.50	D011499	1.50	0.005		0.005
	342.50	344.00	D011500	1.50	<0.005		0.001
	344.00	345.50	D011501	1.50	<0.005		0.001
	345.50	347.00	D011502	1.50	<0.005		0.001
	347.00	348.50	D011503	1.50	0.005		0.005
	348.50	350.00	D011504	1.50	<0.005		0.001
	350.00	351.50	D011506	1.50	0.008		0.008
	351.50	353.00	D011507	1.50	<0.005		0.001
	353.00	354.50	D011508	1.50	<0.005		0.001
	354.50	356.00	D011509	1.50	<0.005		0.001
	356.00	357.50	D011510	1.50	<0.005		0.001
	357.50	359.00	D011511	1.50	0.008		0.008
	359.00	360.50	D011512	1.50	0.006		0.006
	360.50	362.00	D011513	1.50	0.006		0.006
	362.00	363.50	D011514	1.50	0.161		0.161
	363.50	364.70	D011516	1.20	0.612		0.612
	364.70	366.00	D011517	1.30	0.226		0.226
	366.00	367.50	D011518	1.50	0.159		0.159
	367.50	369.00	D011519	1.50	0.056		0.056
	369.00	370.50	D011520	1.50	0.040		0.040
	370.50	372.00	D011521	1.50	0.037		0.037
	372.00	373.50	D011522	1.50	0.012		0.012
	373.50	375.00	D011523	1.50	0.056		0.056
	375.00	376.50	D011524	1.50	0.020		0.020
	376.50	378.00	D011526	1.50	0.056		0.056
	378.00	379.50	D011527	1.50	0.142		0.142
	379.50	381.00	D011528	1.50	0.080		0.080
	381.00	382.50	D011529	1.50	0.195		0.195
	382.50	384.00	D011530	1.50	0.140		0.140
	384.00	385.50	D011531	1.50	0.009		0.009
	385.50	387.00	D011532	1.50	0.072		0.072
	387.00	388.50	D011533	1.50	0.050		0.050

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	388.50	390.00	D011534	1.50	0.022		0.022
	390.00	391.50	D011536	1.50	<0.005		0.001
	391.50	393.00	D011537	1.50	0.005		0.005
	393.00	394.50	D011538	1.50	<0.005		0.001
	394.50	396.00	D011539	1.50	0.052		0.052
	396.00	397.50	D011540	1.50	0.016		0.016
	397.50	399.00	D011541	1.50	0.101		0.101
	399.00	400.50	D011542	1.50	0.126		0.126
	400.50	402.00	D011543	1.50	<0.005		0.001
	402.00	403.50	D011544	1.50	0.271		0.271
	403.50	405.00	D011546	1.50	<0.005		0.001
	405.00	406.50	D011547	1.50	0.096		0.096
	406.50	408.00	D011548	1.50	0.136		0.136
	408.00	409.50	D011549	1.50	0.048		0.048
	409.50	411.00	D011550	1.50	0.187		0.187
	411.00	412.50	D011551	1.50	<0.005		0.001
	412.50	414.00	D011552	1.50	<0.005		0.001
	414.00	415.50	D011553	1.50	<0.005		0.001
	415.50	417.00	D011554	1.50	<0.005		0.001
	417.00	418.50	D011556	1.50	<0.005		0.001
	418.50	420.00	D011557	1.50	<0.005		0.001
	420.00	421.20	D011558	1.20	0.021		0.021
	421.20	422.70	D011559	1.50	1.245		1.245
	422.70	424.30	D011560	1.60	0.009		0.009
	424.30	426.00	D011561	1.70	0.009		0.009
	426.00	427.00	D011562	1.00	<0.005		0.001
	427.00	428.50	D011563	1.50	0.187		0.187
	428.50	430.00	D011564	1.50	<0.005		0.001
	430.00	431.50	D011566	1.50	0.022		0.022
	431.50	433.00	D011567	1.50	0.005		0.005
	433.00	434.50	D011568	1.50	0.013		0.013
	434.50	435.70	D011569	1.20	<0.005		0.001
	435.70	436.70	D011570	1.00	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	436.70	438.00	D011571	1.30	1.425		1.425
	438.00	439.10	D011572	1.10	0.564		0.564
	439.10	440.00	D011573	0.90	0.138		0.138
	440.00	441.00	D011574	1.00	1.825		1.825
	441.00	442.50	D011576	1.50	0.744		0.744
	442.50	444.00	D011577	1.50	0.009		0.009
	444.00	445.50	D011578	1.50	0.021		0.021
	445.50	447.00	D011579	1.50	0.055		0.055
	447.00	448.50	D011580	1.50	<0.005		0.001
	448.50	450.00	D011581	1.50	<0.005		0.001
	450.00	451.50	D011582	1.50	<0.005		0.001
	451.50	453.00	D011583	1.50	<0.005		0.001
	453.00	454.50	D011584	1.50	<0.005		0.001
	454.50	456.00	D011586	1.50	<0.005		0.001
	456.00	457.00	D011587	1.00	<0.005		0.001
	457.00	458.00	D011588	1.00	<0.005		0.001
458.00	Fin du sondage Nombre d'échantillons : 310 Nombre d'échantillons QAQC : 34 Longueur totale échantillonnée : 454.30						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
17.50	19.00	D011255	D011254	1.50	1.090	1.090
31.00	31.00	D011265	M1	0.00	<0.005	0.001
44.50	46.00	D011275	D011274	1.50	0.028	0.028
56.30	56.30	D011285	B4	0.00	2.580	2.580
70.00	71.50	D011295	D011294	1.50	0.005	0.005
83.50	83.50	D011305	M1	0.00	<0.005	0.001
97.00	98.50	D011315	D011314	1.50	0.124	0.124
110.50	110.50	D011325	C4	0.00	1.330	1.330
124.00	125.60	D011335	D011334	1.60	<0.005	0.001
137.00	137.00	D011345	M1	0.00	0.013	0.013
149.50	151.00	D011355	D011354	1.50	1.275	1.275
163.00	163.00	D011365	D2	0.00	0.817	0.817
176.50	178.00	D011375	D011374	1.50	<0.005	0.001
190.00	190.00	D011385	M1	0.00	<0.005	0.001
202.50	204.00	D011395	D011394	1.50	<0.005	0.001
216.00	216.00	D011405	F2	0.00	7.620	8.240
228.50	230.00	D011415	D011414	1.50	<0.005	0.001
241.50	241.50	D011425	M1	0.00	<0.005	0.001
254.00	255.50	D011435	D011434	1.50	<0.005	0.001
267.50	267.50	D011445	G2	0.00	4.010	4.010
281.00	282.50	D011455	D011454	1.50	<0.005	0.001
294.50	294.50	D011465	H	0.00	1.030	1.030
308.00	309.50	D011475	D011474	1.50	0.013	0.013
321.50	321.50	D011485	A3	0.00	0.601	0.601
335.00	336.50	D011495	D011494	1.50	0.010	0.010
348.50	348.50	D011505	M1	0.00	<0.005	0.001
362.00	363.50	D011515	D011514	1.50	0.125	0.125
375.00	375.00	D011525	B4	0.00	2.490	2.490
388.50	390.00	D011535	D011534	1.50	0.026	0.026
402.00	402.00	D011545	M1	0.00	<0.005	0.001
415.50	417.00	D011555	D011554	1.50	<0.005	0.001
428.50	430.00	D011565	C4	1.50	1.330	1.330
440.00	441.00	D011575	D011574	1.00	1.825	1.825

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
453.00	453.00	D011585	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-133**

Titre minier :

Section :                      630900

Canton :

Niveau :

Rang :

Place de travail :            MALARTIC

Foré par :                      Bradley

Lot :

Décrit par :                    Guy Gbaguidi

Du :                              2010-03-13

Date de description :

Au :                              2010-03-22

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -90.00°  
 Longueur :                    476.10 m

Est	630 900.0
Nord	5 374 312.0
Élévation	311.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	1.00	357.50°	-58.50°	Non
Reflex	4.00	357.50°	-58.40°	Non
Reflex	7.00	357.40°	-58.40°	Non
Reflex	10.00	357.30°	-58.50°	Non
Reflex	13.00	357.40°	-58.40°	Non
Reflex	16.00	359.60°	-58.50°	Oui
Reflex	19.00	358.90°	-58.50°	Non
Reflex	22.00	358.00°	-58.50°	Non
Reflex	25.00	358.20°	-58.40°	Non
Reflex	28.00	357.90°	-58.40°	Non
Reflex	31.00	357.80°	-58.30°	Non
Reflex	34.00	357.80°	-58.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	37.00	358.10°	-58.10°	Non
Reflex	40.00	358.10°	-58.10°	Non
Reflex	43.00	358.10°	-58.30°	Non
Reflex	46.00	358.10°	-58.30°	Non
Reflex	49.00	358.40°	-58.40°	Non
Reflex	52.00	358.30°	-58.40°	Non
Reflex	55.00	358.60°	-58.40°	Non
Reflex	58.00	356.50°	-58.40°	Non
Reflex	61.00	359.00°	-58.40°	Non
Reflex	64.00	359.10°	-58.50°	Non
Reflex	67.00	359.30°	-58.50°	Non
Reflex	70.00	359.40°	-58.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	73.00	359.80°	-58.60°	Non	Reflex	172.00	357.60°	-57.50°	Non
Reflex	76.00	359.40°	-58.60°	Non	Reflex	175.00	357.40°	-57.40°	Non
Reflex	79.00	359.40°	-58.50°	Non	Reflex	178.00	357.30°	-57.50°	Non
Reflex	82.00	359.40°	-58.60°	Non	Reflex	181.00	357.20°	-57.40°	Non
Reflex	85.00	359.50°	-58.60°	Non	Reflex	184.00	357.10°	-57.40°	Non
Reflex	88.00	359.40°	-58.60°	Non	Reflex	187.00	356.90°	-57.30°	Non
Reflex	91.00	359.20°	-58.50°	Non	Reflex	190.00	356.80°	-57.30°	Non
Reflex	94.00	358.50°	-58.40°	Non	Reflex	193.00	356.70°	-57.30°	Non
Reflex	97.00	358.30°	-58.30°	Non	Reflex	196.00	356.70°	-57.30°	Non
Reflex	100.00	357.40°	-58.30°	Non	Reflex	199.00	356.60°	-57.30°	Non
Reflex	103.00	358.30°	-58.30°	Non	Reflex	202.00	356.60°	-57.20°	Non
Reflex	106.00	358.70°	-58.20°	Non	Reflex	205.00	356.60°	-57.20°	Non
Reflex	109.00	358.40°	-58.00°	Non	Reflex	208.00	356.50°	-57.10°	Non
Reflex	112.00	358.60°	-57.90°	Non	Reflex	211.00	356.40°	-57.20°	Non
Reflex	115.00	358.50°	-58.00°	Non	Reflex	214.00	356.20°	-57.10°	Non
Reflex	118.00	358.60°	-58.00°	Non	Reflex	217.00	355.60°	-57.10°	Non
Reflex	121.00	358.60°	-58.00°	Non	Reflex	220.00	355.90°	-57.10°	Non
Reflex	124.00	359.30°	-58.00°	Non	Reflex	223.00	358.60°	-57.10°	Non
Reflex	127.00	358.30°	-58.00°	Non	Reflex	226.00	354.50°	-57.00°	Oui
Reflex	130.00	358.60°	-57.90°	Non	Reflex	229.00	0.10°	-57.10°	Non
Reflex	133.00	358.60°	-57.90°	Non	Reflex	232.00	358.90°	-57.00°	Non
Reflex	136.00	358.40°	-57.90°	Non	Reflex	235.00	357.30°	-57.00°	Non
Reflex	139.00	358.30°	-57.90°	Non	Reflex	238.00	0.60°	-57.00°	Non
Reflex	142.00	358.20°	-57.80°	Non	Reflex	241.00	355.40°	-56.80°	Non
Reflex	145.00	358.10°	-57.80°	Non	Reflex	244.00	356.80°	-56.60°	Non
Reflex	148.00	358.10°	-57.70°	Non	Reflex	247.00	354.20°	-56.60°	Non
Reflex	151.00	357.90°	-57.70°	Non	Reflex	250.00	357.40°	-56.60°	Non
Reflex	154.00	357.90°	-57.70°	Non	Reflex	253.00	359.20°	-56.60°	Non
Reflex	157.00	358.20°	-57.70°	Non	Reflex	256.00	359.70°	-56.50°	Non
Reflex	160.00	358.10°	-57.80°	Non	Reflex	259.00	359.40°	-56.50°	Non
Reflex	163.00	358.00°	-57.70°	Non	Reflex	262.00	358.90°	-56.50°	Non
Reflex	166.00	357.90°	-57.70°	Non	Reflex	265.00	358.90°	-56.50°	Non
Reflex	169.00	357.80°	-57.60°	Non	Reflex	268.00	0.50°	-56.50°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	271.00	359.50°	-56.50°	Non	Reflex	370.00	0.50°	-55.80°	Non
Reflex	274.00	2.00°	-56.50°	Non	Reflex	373.00	0.90°	-55.70°	Non
Reflex	277.00	1.20°	-56.50°	Non	Reflex	376.00	359.30°	-55.70°	Non
Reflex	280.00	2.10°	-56.50°	Non	Reflex	379.00	358.70°	-55.70°	Non
Reflex	283.00	358.60°	-56.50°	Non	Reflex	382.00	357.00°	-55.70°	Non
Reflex	286.00	2.50°	-56.50°	Non	Reflex	385.00	358.80°	-55.70°	Non
Reflex	289.00	0.10°	-56.40°	Non	Reflex	388.00	0.70°	-55.70°	Non
Reflex	292.00	359.20°	-56.50°	Non	Reflex	391.00	0.30°	-55.50°	Non
Reflex	295.00	0.40°	-56.40°	Non	Reflex	394.00	0.60°	-55.50°	Non
Reflex	298.00	359.70°	-56.40°	Non	Reflex	397.00	358.50°	-55.40°	Non
Reflex	301.00	359.00°	-56.40°	Non	Reflex	400.00	358.40°	-55.40°	Non
Reflex	304.00	359.50°	-56.30°	Non	Reflex	403.00	1.20°	-55.50°	Non
Reflex	307.00	358.00°	-56.30°	Non	Reflex	406.00	358.70°	-55.10°	Non
Reflex	310.00	357.70°	-56.30°	Non	Reflex	409.00	0.80°	-55.20°	Non
Reflex	313.00	358.10°	-56.20°	Non	Reflex	412.00	359.40°	-55.20°	Non
Reflex	316.00	358.90°	-56.20°	Non	Reflex	415.00	359.80°	-55.20°	Non
Reflex	319.00	357.90°	-56.20°	Non	Reflex	418.00	1.60°	-55.10°	Non
Reflex	322.00	358.80°	-56.10°	Non	Reflex	421.00	0.70°	-55.20°	Non
Reflex	325.00	358.80°	-56.40°	Non	Reflex	424.00	359.80°	-55.20°	Non
Reflex	328.00	358.10°	-56.00°	Non	Reflex	427.00	1.40°	-55.20°	Non
Reflex	331.00	358.10°	-55.90°	Non	Reflex	430.00	0.40°	-55.20°	Non
Reflex	334.00	358.80°	-55.90°	Non	Reflex	433.00	4.20°	-55.20°	Oui
Reflex	337.00	358.40°	-55.80°	Non	Reflex	436.00	0.40°	-55.00°	Non
Reflex	340.00	359.10°	-55.80°	Non	Reflex	439.00	0.10°	-55.00°	Non
Reflex	343.00	357.80°	-55.70°	Non	Reflex	442.00	0.00°	-55.00°	Non
Reflex	346.00	357.90°	-55.80°	Non	Reflex	445.00	2.50°	-54.90°	Non
Reflex	349.00	359.20°	-55.70°	Non	Reflex	448.00	0.80°	-54.90°	Non
Reflex	352.00	358.20°	-55.70°	Non	Reflex	451.00	3.20°	-54.90°	Non
Reflex	355.00	0.30°	-55.70°	Non	Reflex	454.00	2.10°	-54.90°	Non
Reflex	358.00	359.60°	-55.70°	Non	Reflex	457.00	1.50°	-54.80°	Non
Reflex	361.00	360.00°	-55.70°	Non	Reflex	460.00	1.60°	-54.80°	Non
Reflex	364.00	0.60°	-55.70°	Non	Reflex	463.00	1.40°	-54.80°	Non
Reflex	367.00	359.60°	-55.70°	Non	Reflex	466.00	2.40°	-54.80°	Non



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT						
		<b>Mort-terrain</b>						
3.00	87.10	SY; POR	3.00	4.50	D010890	1.50	0.378	0.378
		<b>Syénite; Porphyrique</b>						
		Syénite porphyrique, altérée en potassium, localement carbonatée, phénocristaux de plagioclase fins à grossiers, parfois zonés et séricitisés.						
			4.50	6.00	D010891	1.50	0.168	0.168
			6.00	7.50	D010892	1.50	0.068	0.068
			7.50	9.00	D010893	1.50	1.085	1.085
			9.00	10.50	D010894	1.50	0.289	0.289
			10.50	12.00	D010896	1.50	0.027	0.027
			12.00	13.50	D010897	1.50	0.008	0.008
			13.50	15.00	D010898	1.50	1.060	1.060
			15.00	16.50	D010899	1.50	0.046	0.046
			16.50	18.00	D010900	1.50	0.207	0.207
			18.00	19.50	D010901	1.50	0.009	0.009
			19.50	21.00	D010902	1.50	0.006	0.006
			21.00	22.50	D010903	1.50	<0.005	0.001
			22.50	24.00	D010904	1.50	0.175	0.175
			24.00	25.50	D010906	1.50	0.304	0.304
			25.50	27.00	D010907	1.50	0.497	0.497
			27.00	28.50	D010908	1.50	0.049	0.049
			28.50	30.00	D010909	1.50	0.254	0.254
			30.00	31.50	D010910	1.50	1.035	1.035
			31.50	33.00	D010911	1.50	0.867	0.867
			33.00	34.50	D010912	1.50	<0.005	0.001
			34.50	36.00	D010913	1.50	0.049	0.049
			36.00	37.50	D010914	1.50	0.021	0.021
			37.50	39.00	D010916	1.50	<0.005	0.001
			39.00	40.50	D010917	1.50	0.007	0.007
			40.50	42.00	D010918	1.50	0.050	0.050
			42.00	43.50	D010919	1.50	0.755	0.755
			43.50	45.00	D010920	1.50	0.234	0.234
			45.00	46.50	D010921	1.50	0.038	0.038
			46.50	48.00	D010922	1.50	0.025	0.025
			48.00	49.50	D010923	1.50	0.032	0.032
			49.50	51.00	D010924	1.50	0.009	0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			51.00	52.50	D010926	1.50		0.042		0.042
			52.50	54.00	D010927	1.50		0.242		0.242
			54.00	55.50	D010928	1.50		0.031		0.031
			55.50	57.00	D010929	1.50		0.038		0.038
			57.00	58.50	D010930	1.50		1.005		1.005
			58.50	60.00	D010931	1.50		0.008		0.008
			60.00	61.50	D010932	1.50		0.012		0.012
			61.50	63.00	D010933	1.50		0.008		0.008
			63.00	64.50	D010934	1.50		0.020		0.020
			64.50	66.00	D010936	1.50		<0.005		0.001
			66.00	67.50	D010937	1.50		0.007		0.007
			67.50	69.00	D010938	1.50		<0.005		0.001
			69.00	70.50	D010939	1.50		0.024		0.024
			70.50	72.00	D010940	1.50		0.047		0.047
			72.00	73.50	D010941	1.50		0.242		0.242
			73.50	75.00	D010942	1.50		<0.005		0.001
			75.00	76.50	D010943	1.50		0.017		0.017
			76.50	78.00	D010944	1.50		0.012		0.012
			78.00	79.50	D010946	1.50		0.046		0.046
			79.50	81.00	D010947	1.50		0.017		0.017
			81.00	82.50	D010948	1.50		0.148		0.148
			82.50	84.00	D010949	1.50		<0.005		0.001
			84.00	85.50	D010950	1.50		<0.005		0.001
			85.50	87.10	D010951	1.60		0.032		0.032
87.10	90.00	TU	87.10	88.50	D010952	1.40		<0.005		0.001
		<b>Tuf à cendre/lapillis 45°</b>	88.50	90.00	D010953	1.50		<0.005		0.001
		Tuf à cendre/lapillis intermédiaire.								
90.00	101.30	SY; POR	90.00	91.50	D010954	1.50		0.095		0.095
		<b>Syénite 30°; Porphyrique</b>	91.50	93.00	D010956	1.50		0.060		0.060
		Syénite porphyrique altérée en potassium, faiblement carbonatée, localement séricitisée, silicifié et bréchique de 99.2 à 101.3 m.	93.00	94.50	D010957	1.50		0.015		0.015
			94.50	96.00	D010958	1.50		0.029		0.029
			96.00	97.50	D010959	1.50		0.036		0.036
96.40	96.50	FAI	97.50	99.20	D010960	1.70		0.249		0.249
		<b>Faille</b>								

Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
99.20	101.30	Boue de faille.									
		SY; CAT	99.20	100.20	D010961	1.00	2.540		2.540		
		<b>Syénite 35°; Cataclasée</b>	100.20	101.30	D010962	1.10	3.430		3.430		
		Syénite silicifiée, bréchifiée avec py fine diss.									
101.30	119.00	TU	101.30	103.00	D010963	1.70	0.023		0.023		
		<b>Tuf à lapillis felsique</b>	103.00	104.50	D010964	1.50	0.042		0.042		
		Tuf à lapillis intermédiaire à felsique, silicifié et bréchifié.	104.50	106.00	D010966	1.50	0.093		0.093		
			106.00	107.50	D010967	1.50	0.299		0.299		
			107.50	109.00	D010968	1.50	0.947		0.947		
			109.00	110.50	D010969	1.50	0.420		0.420		
			110.50	112.00	D010970	1.50	1.940		1.940		
			112.00	113.50	D010971	1.50	1.145		1.145		
			113.50	115.00	D010972	1.50	1.735		1.735		
			115.00	116.50	D010973	1.50	3.070		3.070		
			116.50	118.00	D010974	1.50	2.910		2.910		
			118.00	119.00	D010976	1.00	0.861		0.861		
		119.00	476.10	SY	119.00	120.50	D010977	1.50	0.449		0.449
				<b>Syénite</b>	120.50	122.00	D010978	1.50	0.639		0.639
Syénite porphyrique, localement séricitisée, localement altérée en potassium, parfois carbonatée, bréchique par endroit.	122.00			123.50	D010979	1.50	0.219		0.219		
	123.50			125.00	D010980	1.50	0.417		0.417		
	125.00			126.50	D010981	1.50	0.161		0.161		
	126.50			128.00	D010982	1.50	0.136		0.136		
	128.00			129.50	D010983	1.50	0.076		0.076		
	129.50			131.00	D010984	1.50	0.013		0.013		
	131.00			132.50	D010986	1.50	0.095		0.095		
	132.50			134.00	D010987	1.50	0.103		0.103		
	134.00			135.50	D010988	1.50	0.175		0.175		
	135.50			137.00	D010989	1.50	0.051		0.051		
	137.00			138.50	D010990	1.50	0.209		0.209		
	138.50			140.00	D010991	1.50	0.009		0.009		
	140.00	141.50	D010992	1.50	0.219		0.219				
	141.50	143.00	D010993	1.50	0.070		0.070				
	143.00	144.50	D010994	1.50	0.157		0.157				
	144.50	146.00	D010996	1.50	0.145		0.145				

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	146.00	147.50	D010997	1.50	0.473		0.473
	147.50	149.00	D010998	1.50	0.152		0.152
	149.00	150.50	D010999	1.50	0.060		0.060
	150.50	152.00	D011000	1.50	0.159		0.159
	152.00	153.50	D011001	1.50	0.088		0.088
	153.50	155.00	D011002	1.50	0.036		0.036
	155.00	156.50	D011003	1.50	1.985		1.985
	156.50	158.00	D011004	1.50	0.876		0.876
	158.00	159.50	D011006	1.50	0.320		0.320
	159.50	161.00	D011007	1.50	0.672		0.672
	161.00	162.50	D011008	1.50	0.760		0.760
	162.50	164.00	D011009	1.50	0.213		0.213
	164.00	165.50	D011010	1.50	<0.005		0.001
	165.50	167.00	D011011	1.50	<0.005		0.001
	167.00	168.50	D011012	1.50	0.050		0.050
	168.50	170.00	D011013	1.50	0.032		0.032
	170.00	171.50	D011014	1.50	0.056		0.056
	171.50	173.00	D011016	1.50	0.043		0.043
	173.00	174.50	D011017	1.50	0.062		0.062
	174.50	176.00	D011018	1.50	0.110		0.110
	176.00	177.00	D011019	1.00	0.085		0.085
	177.00	178.20	D011020	1.20	<0.005		0.001
	178.20	179.60	D011021	1.40	0.021		0.021
	179.60	181.00	D011022	1.40	0.005		0.005
	181.00	182.50	D011023	1.50	0.016		0.016
	182.50	184.00	D011024	1.50	<0.005		0.001
	184.00	185.50	D011026	1.50	<0.005		0.001
	185.50	187.00	D011027	1.50	0.005		0.005
	187.00	188.50	D011028	1.50	<0.005		0.001
	188.50	190.00	D011029	1.50	0.006		0.006
	190.00	191.50	D011030	1.50	<0.005		0.001
	191.50	193.00	D011031	1.50	0.011		0.011
	193.00	194.50	D011032	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	194.50	196.00	D011033	1.50	<0.005		0.001
	196.00	197.50	D011034	1.50	<0.005		0.001
	197.50	199.00	D011036	1.50	0.008		0.008
	199.00	200.00	D011037	1.00	0.005		0.005
	200.00	201.60	D011038	1.60	0.073		0.073
	201.60	203.20	D011039	1.60	0.006		0.006
	203.20	204.90	D011040	1.70	<0.005		0.001
	204.90	206.50	D011041	1.60	<0.005		0.001
	206.50	208.00	D011042	1.50	<0.005		0.001
	208.00	209.50	D011043	1.50	<0.005		0.001
	209.50	211.00	D011044	1.50	0.183		0.183
	211.00	212.50	D011046	1.50	0.149		0.149
	212.50	214.00	D011047	1.50	0.013		0.013
	214.00	215.50	D011048	1.50	<0.005		0.001
	215.50	217.00	D011049	1.50	0.005		0.005
	217.00	218.50	D011050	1.50	0.031		0.031
	218.50	220.00	D011051	1.50	0.087		0.087
	220.00	221.50	D011052	1.50	0.077		0.077
	221.50	223.00	D011053	1.50	0.183		0.183
	223.00	224.50	D011054	1.50	0.411		0.411
	224.50	226.00	D011056	1.50	0.054		0.054
	226.00	227.50	D011057	1.50	0.013		0.013
	227.50	229.00	D011058	1.50	<0.005		0.001
	229.00	230.00	D011059	1.00	0.042		0.042
	230.00	231.50	D011060	1.50	0.302		0.302
	231.50	233.00	D011061	1.50	0.313		0.313
	233.00	234.50	D011062	1.50	<0.005		0.001
	234.50	236.00	D011063	1.50	<0.005		0.001
	236.00	237.50	D011064	1.50	<0.005		0.001
	237.50	239.00	D011066	1.50	0.056		0.056
	239.00	240.00	D011067	1.00	0.124		0.124
	240.00	241.60	D011068	1.60	0.110		0.110
	241.60	243.00	D011069	1.40	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	243.00	244.50	D011070	1.50	0.005		0.005
	244.50	246.00	D011071	1.50	0.013		0.013
	246.00	247.50	D011072	1.50	<0.005		0.001
	247.50	249.00	D011073	1.50	<0.005		0.001
	249.00	250.00	D011074	1.00	<0.005		0.001
	250.00	251.30	D011076	1.30	<0.005		0.001
	251.30	253.00	D011077	1.70	0.016		0.016
	253.00	254.00	D011078	1.00	0.131		0.131
	254.00	255.50	D011079	1.50	<0.005		0.001
	255.50	257.00	D011080	1.50	0.010		0.010
	257.00	258.50	D011081	1.50	<0.005		0.001
	258.50	260.00	D011082	1.50	<0.005		0.001
	260.00	261.50	D011083	1.50	0.007		0.007
	261.50	263.00	D011084	1.50	0.052		0.052
	263.00	264.50	D011086	1.50	0.005		0.005
	264.50	266.00	D011087	1.50	0.005		0.005
	266.00	267.50	D011088	1.50	<0.005		0.001
	267.50	269.00	D011089	1.50	0.008		0.008
	269.00	270.50	D011090	1.50	<0.005		0.001
	270.50	272.00	D011091	1.50	<0.005		0.001
	272.00	273.50	D011092	1.50	<0.005		0.001
	273.50	275.00	D011093	1.50	<0.005		0.001
	275.00	276.50	D011094	1.50	<0.005		0.001
	276.50	278.00	D011096	1.50	<0.005		0.001
	278.00	279.00	D011097	1.00	<0.005		0.001
	279.00	280.00	D011098	1.00	<0.005		0.001
	280.00	281.50	D011099	1.50	0.235		0.235
	281.50	283.00	D011100	1.50	0.006		0.006
	283.00	284.50	D011101	1.50	0.008		0.008
	284.50	286.00	D011102	1.50	<0.005		0.001
	286.00	287.50	D011103	1.50	<0.005		0.001
	287.50	289.00	D011104	1.50	<0.005		0.001
	289.00	290.50	D011106	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	290.50	292.00	D011107	1.50	<0.005		0.001
	292.00	293.50	D011108	1.50	<0.005		0.001
	293.50	295.00	D011109	1.50	0.321		0.321
	295.00	296.50	D011110	1.50	<0.005		0.001
	296.50	298.00	D011111	1.50	0.008		0.008
	298.00	299.50	D011112	1.50	0.007		0.007
	299.50	301.00	D011113	1.50	<0.005		0.001
	301.00	302.50	D011114	1.50	0.023		0.023
	302.50	304.00	D011116	1.50	0.024		0.024
	304.00	305.50	D011117	1.50	<0.005		0.001
	305.50	307.00	D011118	1.50	1.100		1.100
	307.00	308.50	D011119	1.50	2.850		2.850
	308.50	310.00	D011120	1.50	0.894		0.894
	310.00	311.50	D011121	1.50	0.226		0.226
	311.50	313.00	D011122	1.50	0.169		0.169
	313.00	314.50	D011123	1.50	0.012		0.012
	314.50	316.00	D011124	1.50	0.022		0.022
	316.00	317.50	D011126	1.50	0.007		0.007
	317.50	319.00	D011127	1.50	<0.005		0.001
	319.00	320.50	D011128	1.50	<0.005		0.001
	320.50	322.00	D011129	1.50	0.005		0.005
	322.00	323.50	D011130	1.50	<0.005		0.001
	323.50	325.00	D011131	1.50	0.008		0.008
	325.00	326.50	D011132	1.50	0.005		0.005
	326.50	328.00	D011133	1.50	<0.005		0.001
	328.00	329.50	D011134	1.50	<0.005		0.001
	329.50	331.00	D011136	1.50	<0.005		0.001
	331.00	332.50	D011137	1.50	<0.005		0.001
	332.50	334.00	D011138	1.50	<0.005		0.001
	334.00	335.50	D011139	1.50	<0.005		0.001
	335.50	337.00	D011140	1.50	<0.005		0.001
	337.00	338.50	D011141	1.50	<0.005		0.001
	338.50	340.00	D011142	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	340.00	341.50	D011143	1.50	<0.005		0.001
	341.50	343.00	D011144	1.50	<0.005		0.001
	343.00	344.50	D011146	1.50	<0.005		0.001
	344.50	346.00	D011147	1.50	<0.005		0.001
	346.00	347.50	D011148	1.50	0.030		0.030
	347.50	349.00	D011149	1.50	<0.005		0.001
	349.00	350.50	D011150	1.50	<0.005		0.001
	350.50	352.00	D011151	1.50	<0.005		0.001
	352.00	353.50	D011152	1.50	<0.005		0.001
	353.50	355.00	D011153	1.50	<0.005		0.001
	355.00	356.50	D011154	1.50	0.007		0.007
	356.50	358.00	D011156	1.50	0.066		0.066
	358.00	359.50	D011157	1.50	0.065		0.065
	359.50	361.00	D011158	1.50	0.976		0.976
	361.00	362.50	D011159	1.50	<0.005		0.001
	362.50	364.00	D011160	1.50	<0.005		0.001
	364.00	365.50	D011161	1.50	0.019		0.019
	365.50	367.00	D011162	1.50	0.041		0.041
	367.00	368.50	D011163	1.50	<0.005		0.001
	368.50	370.00	D011164	1.50	<0.005		0.001
	370.00	371.50	D011166	1.50	<0.005		0.001
	371.50	373.00	D011167	1.50	<0.005		0.001
	373.00	374.50	D011168	1.50	<0.005		0.001
	374.50	376.00	D011169	1.50	<0.005		0.001
	376.00	377.50	D011170	1.50	0.044		0.044
	377.50	379.00	D011171	1.50	<0.005		0.001
	379.00	380.00	D011172	1.00	0.152		0.152
	380.00	381.00	D011173	1.00	0.072		0.072
	381.00	382.50	D011174	1.50	0.014		0.014
	382.50	384.00	D011176	1.50	<0.005		0.001
	384.00	385.50	D011177	1.50	<0.005		0.001
	385.50	387.00	D011178	1.50	<0.005		0.001
	387.00	388.50	D011179	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	388.50	390.00	D011180	1.50	0.043		0.043
	390.00	391.50	D011181	1.50	0.006		0.006
	391.50	393.00	D011182	1.50	<0.005		0.001
	393.00	394.50	D011183	1.50	<0.005		0.001
	394.50	396.00	D011184	1.50	<0.005		0.001
	396.00	397.50	D011186	1.50	<0.005		0.001
	397.50	399.00	D011187	1.50	<0.005		0.001
	399.00	400.50	D011188	1.50	<0.005		0.001
	400.50	402.00	D011189	1.50	0.007		0.007
	402.00	403.50	D011190	1.50	<0.005		0.001
	403.50	405.00	D011191	1.50	<0.005		0.001
	405.00	406.50	D011192	1.50	<0.005		0.001
	406.50	408.00	D011193	1.50	<0.005		0.001
	408.00	409.50	D011194	1.50	0.005		0.005
	409.50	411.00	D011196	1.50	<0.005		0.001
	411.00	412.50	D011197	1.50	<0.005		0.001
	412.50	414.00	D011198	1.50	<0.005		0.001
	414.00	415.50	D011199	1.50	0.027		0.027
	415.50	417.00	D011200	1.50	0.089		0.089
	417.00	418.50	D011201	1.50	0.031		0.031
	418.50	420.00	D011202	1.50	0.168		0.168
	420.00	421.50	D011203	1.50	0.798		0.798
	421.50	423.00	D011204	1.50	0.135		0.135
	423.00	424.50	D011206	1.50	0.006		0.006
	424.50	426.00	D011207	1.50	0.057		0.057
	426.00	427.50	D011208	1.50	0.005		0.005
	427.50	429.00	D011209	1.50	0.266		0.266
	429.00	430.50	D011210	1.50	0.229		0.229
	430.50	432.00	D011211	1.50	0.548		0.548
	432.00	433.50	D011212	1.50	0.208		0.208
	433.50	435.00	D011213	1.50	0.305		0.305
	435.00	436.50	D011214	1.50	0.066		0.066
	436.50	438.00	D011216	1.50	0.011		0.011

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	438.00	439.50	D011217	1.50	0.117		0.117
	439.50	441.00	D011218	1.50	<0.005		0.001
	441.00	442.50	D011219	1.50	0.021		0.021
	442.50	444.00	D011220	1.50	0.018		0.018
	444.00	445.50	D011221	1.50	0.010		0.010
	445.50	447.00	D011222	1.50	0.018		0.018
	447.00	448.50	D011223	1.50	0.048		0.048
	448.50	450.00	D011224	1.50	0.120		0.120
	450.00	451.50	D011226	1.50	0.043		0.043
	451.50	453.00	D011227	1.50	0.015		0.015
	453.00	454.50	D011228	1.50	0.077		0.077
	454.50	456.00	D011229	1.50	0.048		0.048
	456.00	457.50	D011230	1.50	0.094		0.094
	457.50	459.00	D011231	1.50	0.016		0.016
	459.00	460.50	D011232	1.50	0.008		0.008
	460.50	462.00	D011233	1.50	<0.005		0.001
	462.00	463.50	D011234	1.50	<0.005		0.001
	463.50	465.00	D011236	1.50	<0.005		0.001
	465.00	466.50	D011237	1.50	<0.005		0.001
	466.50	468.00	D011238	1.50	0.270		0.270
	468.00	469.50	D011239	1.50	0.580		0.580
	469.50	471.00	D011240	1.50	1.300		1.300
	471.00	472.50	D011241	1.50	0.030		0.030
	472.50	474.00	D011242	1.50	<0.005		0.001
	474.00	475.00	D011243	1.00	<0.005		0.001
	475.00	476.10	D011244	1.10	0.793		0.793
476.10	Fin du sondage Nombre d'échantillons : 320 Nombre d'échantillons QAQC : 35 Longueur totale échantillonnée : 473.10						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.00	10.50	D010895	D010894	1.50	0.325	0.325
22.50	22.50	D010905	G2	0.00	4.030	4.030
36.00	37.50	D010915	D010914	1.50	0.033	0.033
49.50	49.50	D010925	M1	0.00	<0.005	0.001
63.00	64.50	D010935	D010934	1.50	0.006	0.006
76.50	76.50	D010945	H	0.00	0.985	0.985
90.00	91.50	D010955	D010954	1.50	0.091	0.091
103.00	103.00	D010965	A3	0.00	0.611	0.611
116.50	118.00	D010975	D010974	1.50	2.970	2.970
129.50	129.50	D010985	M1	0.00	<0.005	0.001
143.00	144.50	D010995	D010994	1.50	0.170	0.170
156.50	156.50	D011005	B4	0.00	2.530	2.530
170.00	171.50	D011015	D011014	1.50	0.050	0.050
182.50	182.50	D011025	M1	0.00	<0.005	0.001
196.00	197.50	D011035	D011034	1.50	<0.005	0.001
209.50	209.50	D011045	C4	0.00	1.370	1.370
223.00	224.50	D011055	D011054	1.50	0.278	0.278
236.00	236.00	D011065	M1	0.00	<0.005	0.001
249.00	250.00	D011075	D011074	1.00	<0.005	0.001
261.50	261.50	D011085	D2	0.00	0.847	0.847
275.00	276.50	D011095	D011094	1.50	<0.005	0.001
287.50	287.50	D011105	M1	0.00	<0.005	0.001
301.00	302.50	D011115	D011114	1.50	0.016	0.016
314.50	314.50	D011125	F2	0.00	8.540	8.540
328.00	329.50	D011135	D011134	1.50	<0.005	0.001
341.50	341.50	D011145	M1	0.00	<0.005	0.001
355.00	356.50	D011155	D011154	1.50	0.005	0.005
368.50	368.50	D011165	G2	0.00	3.950	3.950
381.00	382.50	D011175	D011174	1.50	0.014	0.014
394.50	394.50	D011185	M1	0.00	<0.005	0.001
408.00	409.50	D011195	D011194	1.50	<0.005	0.001
421.50	421.50	D011205	H	0.00	0.951	0.951
435.00	436.50	D011215	D011214	1.50	0.060	0.060

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
448.50	448.50	D011225	A3	0.00	0.623	0.623
462.00	463.50	D011235	D011234	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-134**

Titre minier :

Section :                      630 900

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-03-22

Date de description :      2010-04-26

Au :                      2010-03-29

Collet

UTM

Azimut :                0.00°

Plongée :              -60.00°

Longueur :            476.00 m

Est                      630 900.2

Nord                    5 374 260.0

Élévation              308.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	14.40°	-58.20°	Oui
Reflex	5.00	3.00°	-58.40°	Non
Reflex	8.00	4.00°	-60.00°	Non
Reflex	11.00	3.90°	-60.00°	Non
Reflex	14.00	3.30°	-59.20°	Non
Reflex	17.00	3.80°	-59.90°	Non
Reflex	20.00	3.80°	-60.00°	Non
Reflex	23.00	2.90°	-59.00°	Non
Reflex	26.00	3.80°	-60.00°	Non
Reflex	29.00	3.60°	-59.90°	Non
Reflex	32.00	3.90°	-60.10°	Non
Reflex	35.00	4.00°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	3.40°	-59.60°	Non
Reflex	41.00	4.10°	-60.30°	Non
Reflex	44.00	4.00°	-60.20°	Non
Reflex	47.00	8.40°	-63.70°	Oui
Reflex	50.00	4.30°	-60.30°	Non
Reflex	53.00	4.20°	-60.20°	Non
Reflex	56.00	4.40°	-60.30°	Non
Reflex	59.00	4.50°	-60.40°	Non
Reflex	62.00	4.50°	-60.40°	Non
Reflex	65.00	4.50°	-60.40°	Non
Reflex	68.00	9.80°	-65.30°	Oui
Reflex	71.00	6.20°	-61.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	5.10°	-60.50°	Non	Reflex	173.00	5.30°	-57.70°	Non
Reflex	77.00	4.80°	-60.30°	Non	Reflex	176.00	5.30°	-57.70°	Non
Reflex	80.00	5.30°	-60.20°	Non	Reflex	179.00	5.50°	-57.60°	Non
Reflex	83.00	5.00°	-60.10°	Non	Reflex	182.00	5.50°	-57.60°	Non
Reflex	86.00	5.10°	-59.80°	Non	Reflex	185.00	5.50°	-57.60°	Non
Reflex	89.00	5.00°	-59.90°	Non	Reflex	188.00	5.50°	-57.50°	Non
Reflex	92.00	5.20°	-59.80°	Non	Reflex	191.00	5.40°	-57.50°	Non
Reflex	95.00	5.30°	-59.80°	Non	Reflex	194.00	5.40°	-57.40°	Non
Reflex	98.00	5.50°	-59.70°	Non	Reflex	197.00	5.40°	-57.60°	Non
Reflex	101.00	5.70°	-59.60°	Non	Reflex	200.00	5.10°	-57.30°	Non
Reflex	104.00	6.20°	-59.80°	Non	Reflex	203.00	4.90°	-57.10°	Non
Reflex	107.00	6.00°	-59.60°	Non	Reflex	206.00	4.50°	-56.90°	Non
Reflex	110.00	5.90°	-59.40°	Non	Reflex	209.00	4.50°	-56.90°	Non
Reflex	113.00	6.00°	-59.30°	Non	Reflex	212.00	4.20°	-56.80°	Non
Reflex	116.00	4.90°	-58.00°	Non	Reflex	215.00	4.40°	-56.80°	Non
Reflex	119.00	6.00°	-59.20°	Non	Reflex	218.00	4.40°	-56.90°	Non
Reflex	122.00	5.50°	-59.00°	Non	Reflex	221.00	4.40°	-56.70°	Non
Reflex	125.00	5.40°	-58.70°	Non	Reflex	224.00	4.50°	-56.70°	Non
Reflex	128.00	5.10°	-58.40°	Non	Reflex	227.00	4.30°	-56.30°	Non
Reflex	131.00	5.00°	-58.20°	Non	Reflex	230.00	4.40°	-56.60°	Non
Reflex	134.00	4.90°	-58.20°	Non	Reflex	233.00	4.40°	-56.50°	Non
Reflex	137.00	5.00°	-58.10°	Non	Reflex	236.00	6.20°	-56.70°	Non
Reflex	140.00	5.00°	-58.10°	Non	Reflex	239.00	6.00°	-56.70°	Non
Reflex	143.00	5.10°	-58.10°	Non	Reflex	242.00	5.80°	-56.70°	Non
Reflex	146.00	4.90°	-58.00°	Non	Reflex	245.00	5.90°	-56.70°	Non
Reflex	149.00	4.80°	-58.00°	Non	Reflex	248.00	6.40°	-56.60°	Non
Reflex	152.00	4.90°	-57.90°	Non	Reflex	251.00	6.00°	-56.60°	Non
Reflex	155.00	5.90°	-59.30°	Non	Reflex	254.00	6.00°	-56.60°	Non
Reflex	158.00	5.00°	-57.80°	Non	Reflex	257.00	5.90°	-56.60°	Non
Reflex	161.00	5.10°	-57.80°	Non	Reflex	260.00	5.80°	-56.60°	Non
Reflex	164.00	5.00°	-57.60°	Non	Reflex	263.00	5.60°	-56.50°	Non
Reflex	167.00	5.10°	-57.60°	Non	Reflex	266.00	5.80°	-56.50°	Non
Reflex	170.00	5.20°	-57.70°	Non	Reflex	269.00	5.70°	-56.50°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.60°	-56.40°	Non
Reflex	275.00	5.50°	-56.30°	Non
Reflex	278.00	5.50°	-56.10°	Non
Reflex	281.00	5.60°	-56.20°	Non
Reflex	284.00	5.80°	-56.00°	Non
Reflex	287.00	7.70°	-55.80°	Non
Reflex	290.00	8.30°	-55.70°	Non
Reflex	293.00	9.00°	-55.70°	Non
Reflex	296.00	7.90°	-55.70°	Non
Reflex	299.00	7.80°	-55.70°	Non
Reflex	302.00	9.20°	-55.50°	Non
Reflex	305.00	7.30°	-55.50°	Non
Reflex	308.00	4.80°	-55.40°	Non
Reflex	311.00	8.30°	-55.30°	Oui
Reflex	314.00	6.80°	-55.30°	Non
Reflex	317.00	4.60°	-55.30°	Oui
Reflex	320.00	7.00°	-55.20°	Non
Reflex	323.00	7.40°	-55.10°	Non
Reflex	326.00	4.90°	-55.10°	Oui
Reflex	329.00	7.90°	-55.00°	Non
Reflex	332.00	9.20°	-54.80°	Non
Reflex	335.00	7.90°	-54.80°	Non
Reflex	338.00	8.90°	-54.90°	Non
Reflex	341.00	8.20°	-54.70°	Non
Reflex	344.00	9.10°	-54.80°	Non
Reflex	347.00	8.70°	-54.80°	Non
Reflex	350.00	9.40°	-54.70°	Non
Reflex	353.00	7.80°	-54.60°	Non
Reflex	356.00	8.20°	-54.50°	Non
Reflex	359.00	9.20°	-54.40°	Non
Reflex	362.00	9.40°	-54.50°	Non
Reflex	365.00	8.40°	-54.50°	Non
Reflex	368.00	8.20°	-54.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	7.90°	-54.60°	Non
Reflex	374.00	7.20°	-54.60°	Non
Reflex	377.00	7.90°	-54.60°	Non
Reflex	380.00	7.70°	-54.60°	Non
Reflex	383.00	6.80°	-54.00°	Non
Reflex	386.00	8.80°	-54.70°	Non
Reflex	389.00	7.80°	-54.60°	Non
Reflex	392.00	8.70°	-54.70°	Non
Reflex	395.00	9.60°	-54.80°	Non
Reflex	398.00	8.80°	-54.60°	Non
Reflex	401.00	8.30°	-54.60°	Non
Reflex	404.00	9.40°	-54.70°	Non
Reflex	407.00	7.80°	-54.20°	Non
Reflex	410.00	3.80°	-54.70°	Oui
Reflex	413.00	5.10°	-54.60°	Non
Reflex	416.00	6.10°	-54.70°	Non
Reflex	419.00	7.50°	-54.40°	Non
Reflex	422.00	7.00°	-54.50°	Non
Reflex	425.00	7.80°	-54.40°	Non
Reflex	428.00	6.90°	-54.40°	Non
Reflex	431.00	8.50°	-54.30°	Non
Reflex	434.00	8.50°	-54.40°	Non
Reflex	437.00	10.60°	-54.50°	Oui
Reflex	440.00	9.00°	-54.50°	Non
Reflex	443.00	9.70°	-54.40°	Non
Reflex	446.00	10.60°	-54.30°	Non
Reflex	449.00	9.20°	-54.40°	Non
Reflex	452.00	10.00°	-54.40°	Non
Reflex	455.00	9.60°	-54.50°	Non
Reflex	458.00	10.50°	-54.50°	Non
Reflex	461.00	6.70°	-54.40°	Oui
Reflex	464.00	8.40°	-54.40°	Non
Reflex	467.00	8.30°	-54.30°	Non



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.00	MT						
		<b>Mort-terrain</b>						
1.00	94.50	SY; POR; FIN	1.00	2.50	D007121	1.50	0.008	0.008
		<b>Syénite; Porphyrique; Grains fins</b>	2.50	4.00	D007122	1.50	0.005	0.005
		Syénite grains fins et porphyrique avec des phénocristaux Xmm à Xcm	4.00	5.50	D007123	1.50	0.029	0.029
		à tendance zonés. Qlq VCB.	5.50	7.00	D007124	1.50	0.031	0.031
			7.00	8.50	D007125	1.50	<0.005	0.001
			8.50	10.00	D007126	1.50	<0.005	0.001
			10.00	11.50	D007128	1.50	<0.005	0.001
			11.50	13.00	D007129	1.50	0.005	0.005
			13.00	14.50	D007130	1.50	<0.005	0.001
			14.50	16.00	D007131	1.50	0.034	0.034
			16.00	17.50	D007132	1.50	0.015	0.015
			17.50	19.00	D007133	1.50	<0.005	0.001
			19.00	20.50	D007134	1.50	<0.005	0.001
			20.50	22.00	D007135	1.50	0.005	0.005
			22.00	23.50	D007136	1.50	<0.005	0.001
			23.50	25.00	D007138	1.50	<0.005	0.001
			25.00	26.50	D007139	1.50	<0.005	0.001
			26.50	28.00	D007140	1.50	0.019	0.019
			28.00	29.50	D007141	1.50	<0.005	0.001
			29.50	31.00	D007143	1.50	<0.005	0.001
			31.00	32.50	D007144	1.50	<0.005	0.001
			32.50	34.00	D007145	1.50	<0.005	0.001
			34.00	35.50	D007146	1.50	<0.005	0.001
			35.50	37.00	D007148	1.50	0.014	0.014
			37.00	38.00	D007149	1.00	<0.005	0.001
			38.00	39.00	D007150	1.00	<0.005	0.001
			39.00	40.50	D007151	1.50	<0.005	0.001
			40.50	42.00	D007152	1.50	<0.005	0.001
			42.00	43.50	D007153	1.50	0.007	0.007
			43.50	45.00	D007154	1.50	0.006	0.006
			45.00	46.50	D007155	1.50	0.008	0.008
			46.50	48.00	D007156	1.50	0.096	0.096

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.00	49.50	D007158	1.50	0.017		0.017
	49.50	51.00	D007159	1.50	<0.005		0.001
	51.00	52.50	D007160	1.50	<0.005		0.001
	52.50	54.00	D007161	1.50	0.044		0.044
	54.00	55.50	D007162	1.50	0.072		0.072
	55.50	57.00	D007163	1.50	0.007		0.007
	57.00	58.50	D007164	1.50	0.045		0.045
	58.50	60.00	D007165	1.50	0.005		0.005
	60.00	61.50	D007166	1.50	0.097		0.097
	61.50	63.00	D007168	1.50	0.035		0.035
	63.00	64.50	D007169	1.50	0.011		0.011
	64.50	66.00	D007170	1.50	<0.005		0.001
	66.00	67.50	D007171	1.50	<0.005		0.001
	67.50	69.00	D007172	1.50	0.107		0.107
	69.00	70.50	D007173	1.50	0.107		0.107
	70.50	72.00	D007174	1.50	0.045		0.045
	72.00	73.50	D007175	1.50	0.070		0.070
	73.50	75.00	D007176	1.50	0.012		0.012
	75.00	76.50	D007178	1.50	0.012		0.012
	76.50	78.00	D007179	1.50	0.008		0.008
	78.00	79.50	D007180	1.50	0.005		0.005
	79.50	81.00	D007181	1.50	0.325		0.325
	81.00	82.50	D007183	1.50	0.017		0.017
	82.50	84.00	D007184	1.50	0.005		0.005
	84.00	85.50	D007185	1.50	0.006		0.006
	85.50	87.00	D007186	1.50	0.024		0.024
	87.00	88.50	D007188	1.50	<0.005		0.001
	88.50	90.00	D007189	1.50	0.018		0.018
	90.00	91.50	D007190	1.50	0.021		0.021
	91.50	93.00	D007191	1.50	0.030		0.030
	93.00	94.50	D007192	1.50	0.353		0.353
94.50	152.00		D007193	1.50	0.006		0.006
			D007194	1.50	0.009		0.009

SY; FIN

**Syénite; Grains fins**

Syénite à grains fins à altération différentielle avec qlq VCB.

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	97.50	99.00	D007195	1.50	0.112		0.112
	99.00	100.50	D007196	1.50	0.189		0.189
	100.50	102.00	D007198	1.50	2.310		2.310
	102.00	103.50	D007199	1.50	0.020		0.020
	103.50	105.00	D007200	1.50	0.025		0.025
	105.00	106.50	D007201	1.50	0.014		0.014
	106.50	108.00	D007202	1.50	0.494		0.494
	108.00	109.50	D007203	1.50	0.030		0.030
	109.50	111.00	D007204	1.50	0.789		0.789
	111.00	112.50	D007205	1.50	0.163		0.163
	112.50	114.00	D007206	1.50	0.009		0.009
	114.00	115.50	D007208	1.50	0.019		0.019
	115.50	117.00	D007209	1.50	1.260		1.260
	117.00	118.50	D007210	1.50	0.025		0.025
	118.50	120.00	D007211	1.50	0.008		0.008
	120.00	121.50	D007212	1.50	0.006		0.006
	121.50	123.00	D007213	1.50	0.011		0.011
	123.00	124.50	D007214	1.50	0.005		0.005
	124.50	126.00	D007215	1.50	<0.005		0.001
	126.00	127.50	D007216	1.50	0.011		0.011
	127.50	129.00	D007218	1.50	0.006		0.006
	129.00	130.50	D007219	1.50	<0.005		0.001
	130.50	132.00	D007220	1.50	<0.005		0.001
	132.00	133.50	D007221	1.50	<0.005		0.001
	133.50	135.00	D007223	1.50	<0.005		0.001
	135.00	136.50	D007224	1.50	<0.005		0.001
	136.50	138.00	D007225	1.50	0.026		0.026
	138.00	139.50	D007226	1.50	0.007		0.007
	139.50	141.00	D007228	1.50	0.037		0.037
	141.00	142.50	D007229	1.50	0.010		0.010
	142.50	144.00	D007230	1.50	<0.005		0.001
	144.00	145.50	D007231	1.50	<0.005		0.001
	145.50	147.00	D007232	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
152.00	153.00	BA; BRC <b>Basalte 25°; Brèche de coulée</b> Basalte bréchifié avec l'inclusion de fragments de syénite.	147.00	148.50	D007233	1.50	0.227		0.227
			148.50	150.00	D007234	1.50	0.008		0.008
			150.00	151.00	D007235	1.00	0.165		0.165
			151.00	152.00	D007236	1.00	0.868		0.868
			152.00	153.00	D007238	1.00	0.183		0.183
153.00	163.50	SY; FIN <b>Syénite 25°; Grains fins</b> Syénite à grains fins avec qlq VCB.	153.00	154.50	D007239	1.50	0.225		0.225
			154.50	156.00	D007240	1.50	0.222		0.222
			156.00	157.50	D007241	1.50	0.012		0.012
			157.50	159.00	D007242	1.50	0.332		0.332
			159.00	160.50	D007243	1.50	0.010		0.010
			160.50	162.00	D007244	1.50	0.013		0.013
			162.00	163.50	D007245	1.50	1.205		1.205
163.50	417.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique avec de phénocristaux Xmm, sub-arrondi à sub-allongé.	163.50	165.00	D007246	1.50	0.913	5.38 3.20	0.913
			165.00	166.50	D007248	1.50	1.445		1.445
			166.50	168.00	D007249	1.50	1.250		1.250
			168.00	169.50	D007250	1.50	0.748		0.748
			169.50	171.00	D007251	1.50	0.549		0.549
			171.00	172.50	D007252	1.50	0.160		0.160
			172.50	174.00	D007253	1.50	0.220		0.220
			174.00	175.50	D007254	1.50	0.986		0.986
			175.50	177.00	D007255	1.50	1.660		1.660
			177.00	178.50	D007256	1.50	5.640		5.380
			178.50	180.00	D007258	1.50	3.420		3.200
			180.00	181.50	D007259	1.50	0.879		0.879
			181.50	183.00	D007260	1.50	0.385		0.385
			183.00	184.50	D007261	1.50	0.715		0.715
			184.50	186.00	D007263	1.50	0.801		0.801
186.00	187.50	D007264	1.50	1.655	1.655				
187.50	189.00	D007265	1.50	1.040	1.040				
189.00	190.50	D007266	1.50	0.319	0.319				
190.50	192.00	D007268	1.50	0.366	0.366				
192.00	193.50	D007269	1.50	0.439	0.439				

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	193.50	195.00	D007270	1.50	1.685		1.685
	195.00	196.50	D007271	1.50	2.180		2.180
	196.50	198.00	D007272	1.50	0.334		0.334
	198.00	199.50	D007273	1.50	0.136		0.136
	199.50	201.00	D007274	1.50	0.411		0.411
	201.00	202.50	D007275	1.50	0.220		0.220
	202.50	204.00	D007276	1.50	0.045		0.045
	204.00	205.50	D007278	1.50	0.235		0.235
	205.50	207.00	D007279	1.50	0.096		0.096
	207.00	208.50	D007280	1.50	0.090		0.090
	208.50	210.00	D007281	1.50	0.016		0.016
	210.00	211.50	D007282	1.50	0.138		0.138
	211.50	213.00	D007283	1.50	0.168		0.168
	213.00	214.50	D007284	1.50	0.165		0.165
	214.50	216.00	D007285	1.50	0.163		0.163
	216.00	217.50	D007286	1.50	0.213		0.213
	217.50	219.00	D007288	1.50	0.180		0.180
	219.00	220.50	D007289	1.50	0.286		0.286
	220.50	222.00	D007290	1.50	0.125		0.125
	222.00	223.50	D007291	1.50	0.117		0.117
	223.50	225.00	D007292	1.50	0.694		0.694
	225.00	226.50	D007293	1.50	0.473		0.473
	226.50	228.00	D007294	1.50	0.372		0.372
	228.00	229.50	D007295	1.50	0.506		0.506
	229.50	231.00	D007296	1.50	1.285		1.285
	231.00	232.50	D007298	1.50	0.819		0.819
	232.50	234.00	D007299	1.50	0.367		0.367
	234.00	235.50	D007300	1.50	0.279		0.279
	235.50	237.00	D007301	1.50	0.520		0.520
	237.00	238.50	D007302	1.50	0.147		0.147
	238.50	240.00	D007303	1.50	0.408		0.408
	240.00	241.50	D007304	1.50	0.102		0.102
	241.50	243.00	D007305	1.50	0.029		0.029

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	243.00	244.50	D007306	1.50	0.072		0.072
	244.50	246.00	D007308	1.50	0.064		0.064
	246.00	247.50	D007309	1.50	0.071		0.071
	247.50	249.00	D007310	1.50	0.069		0.069
	249.00	250.50	D007311	1.50	0.036		0.036
	250.50	252.00	D007312	1.50	0.349		0.349
	252.00	253.50	D007313	1.50	0.010		0.010
	253.50	255.00	D007314	1.50	0.014		0.014
	255.00	256.50	D007315	1.50	<0.005		0.001
	256.50	258.00	D007316	1.50	0.011		0.011
	258.00	259.50	D007318	1.50	0.005		0.005
	259.50	261.00	D007319	1.50	0.006		0.006
	261.00	262.50	D007320	1.50	0.389		0.389
	262.50	264.00	D007321	1.50	0.006		0.006
	264.00	265.50	D007322	1.50	<0.005		0.001
	265.50	267.00	D007323	1.50	<0.005		0.001
	267.00	268.50	D007324	1.50	<0.005		0.001
	268.50	270.00	D007325	1.50	<0.005		0.001
	270.00	271.50	D007326	1.50	<0.005		0.001
	271.50	273.00	D007328	1.50	<0.005		0.001
	273.00	274.50	D007329	1.50	0.029		0.029
	274.50	276.00	D007330	1.50	0.070		0.070
	276.00	277.50	D007331	1.50	0.172		0.172
	277.50	279.00	D007332	1.50	0.032		0.032
	279.00	280.50	D007333	1.50	<0.005		0.001
	280.50	282.00	D007334	1.50	0.012		0.012
	282.00	283.50	D007335	1.50	<0.005		0.001
	283.50	285.00	D007336	1.50	0.031		0.031
	285.00	286.50	D007338	1.50	0.159		0.159
	286.50	288.00	D007339	1.50	<0.005		0.001
	288.00	289.50	D007340	1.50	0.007		0.007
	289.50	291.00	D007341	1.50	0.015		0.015
	291.00	292.50	D007343	1.50	0.021		0.021



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	292.50	294.00	D007344	1.50	<0.005		0.001
	294.00	295.50	D007345	1.50	<0.005		0.001
	295.50	297.00	D007346	1.50	0.008		0.008
	297.00	298.50	D007348	1.50	<0.005		0.001
	298.50	300.00	D007349	1.50	0.010		0.010
	300.00	301.50	D007350	1.50	<0.005		0.001
	301.50	303.00	D007351	1.50	<0.005		0.001
	303.00	304.50	D007352	1.50	0.013		0.013
	304.50	306.00	D007353	1.50	0.017		0.017
	306.00	307.50	D007354	1.50	0.005		0.005
	307.50	309.00	D007355	1.50	0.005		0.005
	309.00	310.50	D007356	1.50	0.042		0.042
	310.50	312.00	D007358	1.50	0.006		0.006
	312.00	313.00	D007359	1.00	0.067		0.067
	313.00	314.50	D007360	1.50	1.155		1.155
	314.50	316.00	D007361	1.50	0.707		0.707
	316.00	317.00	D007362	1.00	0.007		0.007
	317.00	318.00	D007363	1.00	0.006		0.006
	318.00	319.50	D007364	1.50	<0.005		0.001
	319.50	321.00	D007365	1.50	<0.005		0.001
	321.00	322.50	D007366	1.50	0.029		0.029
	322.50	324.00	D007368	1.50	0.010		0.010
	324.00	325.50	D007369	1.50	<0.005		0.001
	325.50	327.00	D007370	1.50	0.124		0.124
	327.00	328.50	D007371	1.50	<0.005		0.001
	328.50	330.00	D007372	1.50	<0.005		0.001
	330.00	331.50	D007373	1.50	<0.005		0.001
	331.50	333.00	D007374	1.50	0.005		0.005
	333.00	334.50	D007375	1.50	0.012		0.012
	334.50	336.00	D007376	1.50	<0.005		0.001
	336.00	337.50	D007378	1.50	0.005		0.005
	337.50	339.00	D007379	1.50	0.009		0.009
	339.00	340.50	D007380	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	340.50	342.00	D007381	1.50	0.007		0.007
	342.00	343.50	D007383	1.50	<0.005		0.001
	343.50	345.00	D007384	1.50	<0.005		0.001
	345.00	346.50	D007385	1.50	0.029		0.029
	346.50	348.00	D007386	1.50	<0.005		0.001
	348.00	349.50	D007388	1.50	0.039		0.039
	349.50	351.00	D007389	1.50	0.051		0.051
	351.00	352.50	D007390	1.50	<0.005		0.001
	352.50	354.00	D007391	1.50	<0.005		0.001
	354.00	355.50	D007392	1.50	<0.005		0.001
	355.50	357.00	D007393	1.50	<0.005		0.001
	357.00	358.50	D007394	1.50	<0.005		0.001
	358.50	360.00	D007395	1.50	<0.005		0.001
	360.00	361.50	D007396	1.50	0.021		0.021
	361.50	363.00	D007398	1.50	0.006		0.006
	363.00	364.50	D007399	1.50	0.065		0.065
	364.50	366.00	D007400	1.50	<0.005		0.001
	366.00	367.50	D007401	1.50	0.009		0.009
	367.50	369.00	D007403	1.50	0.734		0.734
	369.00	370.50	D007404	1.50	0.815		0.815
	370.50	372.00	D007405	1.50	0.066		0.066
	372.00	373.50	D007406	1.50	0.454		0.454
	373.50	375.00	D007408	1.50	0.586		0.586
	375.00	376.50	D007409	1.50	0.367		0.367
	376.50	378.00	D007410	1.50	0.202		0.202
	378.00	379.50	D007411	1.50	<0.005		0.001
	379.50	381.00	D007412	1.50	<0.005		0.001
	381.00	382.50	D007413	1.50	<0.005		0.001
	382.50	384.00	D007414	1.50	<0.005		0.001
	384.00	385.50	D007415	1.50	<0.005		0.001
	385.50	387.00	D007416	1.50	0.030		0.030
	387.00	388.50	D007418	1.50	0.045		0.045
	388.50	390.00	D007419	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	390.00	391.50	D007420	1.50	<0.005		0.001
	391.50	393.00	D007421	1.50	0.023		0.023
	393.00	394.50	D007422	1.50	0.045		0.045
	394.50	396.00	D007423	1.50	0.016		0.016
	396.00	397.50	D007424	1.50	<0.005		0.001
	397.50	399.00	D007425	1.50	<0.005		0.001
	399.00	400.50	D007426	1.50	<0.005		0.001
	400.50	402.00	D007428	1.50	0.011		0.011
	402.00	403.50	D007429	1.50	<0.005		0.001
	403.50	405.00	D007430	1.50	0.005		0.005
	405.00	406.50	D007431	1.50	<0.005		0.001
	406.50	408.00	D007432	1.50	<0.005		0.001
	408.00	409.50	D007433	1.50	<0.005		0.001
	409.50	411.00	D007434	1.50	0.067		0.067
	411.00	412.50	D007435	1.50	0.035		0.035
	412.50	414.00	D007436	1.50	0.332		0.332
	414.00	415.50	D007438	1.50	0.010		0.010
	415.50	417.00	D007439	1.50	<0.005		0.001
417.00	417.00	418.50	D007440	1.50	<0.005		0.001
476.00	418.50	420.00	D007441	1.50	0.005		0.005
	420.00	421.50	D007443	1.50	0.053		0.053
	421.50	423.00	D007444	1.50	<0.005		0.001
	423.00	424.50	D007445	1.50	<0.005		0.001
	424.50	426.00	D007446	1.50	0.008		0.008
	426.00	427.50	D007448	1.50	<0.005		0.001
	427.50	429.00	D007449	1.50	<0.005		0.001
	429.00	430.50	D007450	1.50	0.047		0.047
	430.50	432.00	D007451	1.50	0.142		0.142
	432.00	433.50	D007452	1.50	0.023		0.023
	433.50	435.00	D007453	1.50	<0.005		0.001
	435.00	436.50	D007454	1.50	<0.005		0.001
	436.50	438.00	D007455	1.50	<0.005		0.001
	438.00	439.50	D007456	1.50	<0.005		0.001

SY; FIN

**Syénite; Grains fins**

Syénite à grains fins avec qlq fantômes de phénocristaux et , passage VCB.

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	439.50	441.00	D007458	1.50	<0.005		0.001
	441.00	442.50	D007459	1.50	0.031		0.031
	442.50	444.00	D007460	1.50	<0.005		0.001
	444.00	445.50	D007461	1.50	<0.005		0.001
	445.50	447.00	D007462	1.50	<0.005		0.001
	447.00	448.50	D007463	1.50	<0.005		0.001
	448.50	450.00	D007464	1.50	<0.005		0.001
	450.00	451.50	D007465	1.50	<0.005		0.001
	451.50	453.00	D007466	1.50	<0.005		0.001
	453.00	454.50	D007468	1.50	0.008		0.008
	454.50	456.00	D007469	1.50	<0.005		0.001
	456.00	457.50	D007470	1.50	<0.005		0.001
	457.50	459.00	D007471	1.50	0.172		0.172
	459.00	460.50	D007472	1.50	0.215		0.215
	460.50	462.00	D007473	1.50	0.154		0.154
	462.00	463.50	D007474	1.50	<0.005		0.001
	463.50	465.00	D007475	1.50	0.008		0.008
	465.00	466.50	D007476	1.50	0.024		0.024
	466.50	468.00	D007478	1.50	0.164		0.164
	468.00	469.50	D007479	1.50	0.020		0.020
	469.50	471.00	D007480	1.50	0.020		0.020
	471.00	472.50	D007481	1.50	0.473		0.473
	472.50	474.00	D007483	1.50	<0.005		0.001
	474.00	475.00	D007484	1.00	<0.005		0.001
	475.00	476.00	D007485	1.00	<0.005		0.001
476.00	Fin du sondage Nombre d'échantillons : 320 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 475.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
8.50	10.00	D007127	A3	1.50	0.629	0.629
22.00	23.50	D007137	D007136	1.50	<0.005	0.001
28.00	29.50	D007142	M1	1.50	<0.005	0.001
34.00	35.50	D007147	G2	1.50	4.010	4.060
46.50	48.00	D007157	D007156	1.50	0.074	0.074
60.00	61.50	D007167	C4	1.50	1.365	1.365
73.50	75.00	D007177	D007176	1.50	0.012	0.012
79.50	81.00	D007182	M1	1.50	<0.005	0.001
85.50	87.00	D007187	D2	1.50	0.847	0.847
99.00	100.50	D007197	D007196	1.50	0.194	0.194
112.50	114.00	D007207	F2	1.50	NSS	8.430
126.00	127.50	D007217	D007216	1.50	0.011	0.011
132.00	133.50	D007222	M1	1.50	<0.005	0.001
138.00	139.50	D007227	G2	1.50	4.030	0.000
151.00	152.00	D007237	D007236	1.00	0.797	0.797
163.50	165.00	D007247	H	1.50	1.035	1.035
177.00	178.50	D007257	D007256	1.50	5.660	5.360
183.00	184.50	D007262	M1	1.50	0.005	0.005
189.00	190.50	D007267	A3	1.50	0.626	0.626
202.50	204.00	D007277	D007276	1.50	0.055	0.055
216.00	217.50	D007287	B4	1.50	2.650	2.650
229.50	231.00	D007297	D007296	1.50	1.260	1.260
243.00	244.50	D007307	C4	1.50	1.325	1.325
256.50	258.00	D007317	D007316	1.50	0.028	0.028
270.00	271.50	D007327	D2	1.50	0.863	0.863
283.50	285.00	D007337	D007336	1.50	0.121	0.121
289.50	291.00	D007342	M1	1.50	<0.005	0.001
295.50	297.00	D007347	F2	1.50	8.470	8.580
309.00	310.50	D007357	D007356	1.50	0.047	0.047
321.00	322.50	D007367	G2	1.50		
334.50	336.00	D007377	D007376	1.50	<0.005	0.001
340.50	342.00	D007382	M1	1.50	<0.005	0.001
346.50	348.00	D007387	H	1.50	0.966	0.966

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
360.00	361.50	D007397	D007396	1.50	0.013	0.013
366.00	367.50	D007402	M1	1.50	<0.005	0.001
372.00	373.50	D007407	A3	1.50	0.636	0.636
385.50	387.00	D007417	D007416	1.50	0.026	0.026
399.00	400.50	D007427	H	1.50	0.962	0.962
412.50	414.00	D007437	D007436	1.50	0.118	0.118
418.50	420.00	D007442	M1	1.50	<0.005	0.001
424.50	426.00	D007447	D2	1.50	0.844	0.844
438.00	439.50	D007457	D007456	1.50	<0.005	0.001
451.50	453.00	D007467	B4	1.50	2.550	2.550
465.00	466.50	D007477	D007476	1.50	0.014	0.014
471.00	472.50	D007482	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-135**

Titre minier :

Section :                      630 900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles.KAMTA

Lot :

Du :                              2010-04-03

Date de description :

Au :                              2010-04-06

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      366.51 m

Est	630 900.2
Nord	5 374 409.7
Élévation	311.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	11.40°	-60.00°	Oui
Reflex	5.00	359.60°	-59.90°	Non
Reflex	8.00	359.50°	-60.10°	Non
Reflex	11.00	359.30°	-59.80°	Non
Reflex	14.00	359.30°	-59.80°	Non
Reflex	17.00	359.60°	-59.80°	Non
Reflex	20.00	359.40°	-59.80°	Non
Reflex	23.00	359.60°	-59.70°	Non
Reflex	26.00	359.70°	-59.80°	Non
Reflex	29.00	0.10°	-60.00°	Non
Reflex	32.00	0.20°	-60.00°	Non
Reflex	35.00	0.30°	-60.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.60°	-60.10°	Non
Reflex	41.00	1.10°	-60.00°	Non
Reflex	44.00	1.30°	-59.90°	Non
Reflex	47.00	1.60°	-60.00°	Non
Reflex	50.00	1.60°	-60.00°	Non
Reflex	53.00	1.60°	-60.00°	Non
Reflex	56.00	2.30°	-60.10°	Non
Reflex	59.00	1.80°	-60.10°	Non
Reflex	62.00	1.30°	-60.10°	Non
Reflex	65.00	1.80°	-60.10°	Non
Reflex	68.00	3.00°	-60.20°	Non
Reflex	71.00	2.60°	-60.20°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.60°	-60.20°	Non
Reflex	77.00	3.80°	-60.20°	Non
Reflex	80.00	2.60°	-60.20°	Non
Reflex	83.00	2.80°	-60.20°	Non
Reflex	86.00	1.00°	-60.30°	Non
Reflex	89.00	1.70°	-60.30°	Non
Reflex	92.00	2.90°	-60.30°	Non
Reflex	95.00	4.30°	-60.30°	Non
Reflex	98.00	4.60°	-60.30°	Non
Reflex	101.00	5.10°	-60.30°	Non
Reflex	104.00	2.40°	-60.30°	Non
Reflex	107.00	4.20°	-60.30°	Non
Reflex	110.00	4.10°	-60.30°	Non
Reflex	113.00	4.00°	-60.10°	Non
Reflex	116.00	4.10°	-60.00°	Non
Reflex	119.00	4.10°	-60.00°	Non
Reflex	122.00	4.10°	-60.10°	Non
Reflex	125.00	4.20°	-60.10°	Non
Reflex	128.00	6.10°	-60.00°	Oui
Reflex	131.00	5.60°	-60.00°	Non
Reflex	134.00	5.60°	-60.10°	Non
Reflex	137.00	5.60°	-60.10°	Non
Reflex	140.00	5.60°	-60.00°	Non
Reflex	143.00	5.50°	-59.90°	Non
Reflex	146.00	5.40°	-59.90°	Non
Reflex	149.00	8.00°	-59.80°	Oui
Reflex	152.00	6.90°	-59.90°	Non
Reflex	155.00	5.40°	-59.90°	Non
Reflex	158.00	5.40°	-59.60°	Non
Reflex	161.00	4.90°	-59.40°	Non
Reflex	164.00	4.40°	-59.10°	Non
Reflex	167.00	4.00°	-58.90°	Non
Reflex	170.00	4.10°	-58.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	4.10°	-58.80°	Non
Reflex	176.00	4.20°	-58.80°	Non
Reflex	179.00	4.30°	-58.80°	Non
Reflex	182.00	4.30°	-58.80°	Non
Reflex	185.00	4.30°	-58.70°	Non
Reflex	188.00	4.30°	-58.80°	Non
Reflex	191.00	4.30°	-58.90°	Non
Reflex	194.00	4.30°	-58.90°	Non
Reflex	197.00	4.00°	-58.80°	Non
Reflex	200.00	4.80°	-58.70°	Non
Reflex	203.00	3.70°	-58.60°	Non
Reflex	206.00	3.60°	-58.70°	Non
Reflex	209.00	3.60°	-58.70°	Non
Reflex	212.00	3.40°	-58.70°	Non
Reflex	215.00	4.50°	-58.80°	Non
Reflex	218.00	6.00°	-58.80°	Oui
Reflex	221.00	5.10°	-58.80°	Non
Reflex	224.00	5.40°	-58.90°	Non
Reflex	227.00	4.50°	-58.80°	Non
Reflex	230.00	4.80°	-58.80°	Non
Reflex	233.00	4.70°	-58.80°	Non
Reflex	236.00	4.90°	-58.80°	Non
Reflex	239.00	5.10°	-58.90°	Non
Reflex	242.00	5.20°	-58.80°	Non
Reflex	245.00	4.80°	-58.90°	Non
Reflex	248.00	5.90°	-58.90°	Non
Reflex	251.00	5.60°	-58.90°	Non
Reflex	254.00	7.40°	-59.00°	Oui
Reflex	257.00	6.50°	-58.90°	Non
Reflex	260.00	6.60°	-58.80°	Non
Reflex	263.00	7.10°	-58.70°	Non
Reflex	266.00	6.80°	-58.60°	Non
Reflex	269.00	4.80°	-58.50°	Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	7.20°	-58.40°	Non					
Reflex	275.00	5.80°	-58.30°	Non					
Reflex	278.00	5.30°	-58.10°	Non					
Reflex	281.00	8.00°	-58.00°	Non					
Reflex	284.00	9.20°	-57.90°	Non					
Reflex	287.00	8.00°	-57.80°	Non					
Reflex	290.00	8.20°	-57.70°	Non					
Reflex	293.00	6.90°	-57.60°	Non					
Reflex	296.00	7.70°	-57.50°	Non					
Reflex	299.00	7.20°	-57.50°	Non					
Reflex	302.00	8.30°	-57.40°	Non					
Reflex	305.00	7.60°	-57.20°	Non					
Reflex	308.00	7.60°	-57.00°	Non					
Reflex	311.00	7.10°	-56.90°	Non					
Reflex	314.00	7.30°	-56.80°	Non					
Reflex	317.00	7.60°	-56.80°	Non					
Reflex	320.00	8.10°	-56.70°	Non					
Reflex	323.00	8.40°	-56.60°	Non					
Reflex	326.00	8.80°	-56.40°	Non					
Reflex	329.00	9.20°	-56.30°	Non					
Reflex	332.00	9.30°	-56.20°	Non					
Reflex	335.00	9.40°	-56.00°	Non					
Reflex	338.00	9.40°	-56.00°	Non					
Reflex	341.00	9.30°	-55.80°	Non					
Reflex	344.00	9.30°	-55.70°	Non					
Reflex	347.00	9.30°	-55.50°	Non					
Reflex	350.00	9.30°	-55.40°	Non					
Reflex	353.00	9.20°	-55.20°	Non					
Reflex	356.00	9.40°	-55.00°	Non					
Reflex	359.00	9.60°	-54.90°	Non					
Reflex	362.00	9.60°	-54.70°	Non					
Reflex	365.00	9.50°	-56.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT						
		<b>Mort-terrain</b>						
2.20	307.20	SY; MAS; FIN	2.20	3.50	D002176	1.30	0.698	0.698
		<b>Syénite; Roche massive; Grains fins</b>	3.50	5.00	D002177	1.50	0.057	0.057
		localement cataclasé, phénocristaux automorphe localement 1-2%,	5.00	6.50	D002178	1.50	0.009	0.009
		altération potassique et hématisation, oxyde de carbonâte ocre,	6.50	8.00	D002179	1.50	0.006	0.006
		séricitisation et chloritisation, veinules et cheveux de calcite et QZ cm,	8.00	9.50	D002180	1.50	0.012	0.012
		localement cisailé, PY fine arsénopyrite	9.50	11.00	D002181	1.50	<0.005	0.001
			11.00	12.50	D002182	1.50	0.029	0.029
			12.50	14.00	D002183	1.50	0.024	0.024
			14.00	15.50	D002184	1.50	<0.005	0.001
			15.50	17.00	D002186	1.50	<0.005	0.001
			17.00	18.50	D002187	1.50	0.005	0.005
			18.50	20.00	D002188	1.50	<0.005	0.001
			20.00	21.50	D002189	1.50	0.006	0.006
21.50	22.40	CIS	21.50	23.00	D002190	1.50	0.008	0.008
		<b>Cisaillement 40°</b>	23.00	24.50	D002191	1.50	0.513	0.513
		légèrement cisailé	24.50	26.00	D002192	1.50	0.006	0.006
			26.00	27.50	D002193	1.50	<0.005	0.001
			27.50	29.00	D002194	1.50	<0.005	0.001
			29.00	30.50	D002196	1.50	<0.005	0.001
			30.50	32.00	D002197	1.50	0.029	0.029
			32.00	33.50	D002198	1.50	0.010	0.010
			33.50	35.00	D002199	1.50	0.153	0.153
			35.00	36.50	D002200	1.50	<0.005	0.001
			36.50	38.00	D002201	1.50	<0.005	0.001
			38.00	39.50	D002202	1.50	<0.005	0.001
			39.50	40.90	D002203	1.40	0.013	0.013
			40.90	42.50	D002204	1.60	<0.005	0.001
			42.50	44.00	D002206	1.50	<0.005	0.001
			44.00	45.00	D002207	1.00	<0.005	0.001
			45.00	46.10	D002208	1.10	<0.005	0.001
			46.10	47.60	D002209	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
65.50	73.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> phénocristaux de FP automorphe 0.2-2 cm localement altéré en calcite, forte hématisation,	47.60	49.30	D002210	1.70	<0.005		0.001
			49.30	50.50	D002211	1.20	<0.005		0.001
			50.50	52.00	D002212	1.50	0.005		0.005
			52.00	53.50	D002213	1.50	0.005		0.005
			53.50	55.00	D002214	1.50	<0.005		0.001
			55.00	56.50	D002216	1.50	<0.005		0.001
			56.50	58.00	D002217	1.50	<0.005		0.001
			58.00	59.50	D002218	1.50	<0.005		0.001
			59.50	61.00	D002219	1.50	<0.005		0.001
			61.00	62.50	D002220	1.50	<0.005		0.001
			62.50	64.00	D002221	1.50	<0.005		0.001
			64.00	65.50	D002222	1.50	<0.005		0.001
			65.50	67.00	D002223	1.50	0.020		0.020
			67.00	68.50	D002224	1.50	0.009		0.009
			68.50	70.00	D002226	1.50	0.044		0.044
			70.00	71.50	D002227	1.50	0.009		0.009
			71.50	73.00	D002228	1.50	<0.005		0.001
			73.00	74.50	D002229	1.50	0.089		0.089
			74.50	76.00	D002230	1.50	0.056		0.056
			76.00	77.50	D002231	1.50	0.013		0.013
			77.50	79.00	D002232	1.50	0.005		0.005
			79.00	80.50	D002233	1.50	<0.005		0.001
			80.50	82.00	D002234	1.50	<0.005		0.001
			82.00	83.50	D002236	1.50	0.017		0.017
			83.50	85.00	D002237	1.50	<0.005		0.001
			85.00	86.50	D002238	1.50	0.008		0.008
86.50	88.00	D002239	1.50	0.086		0.086			
88.00	89.50	D002240	1.50	<0.005		0.001			
89.50	91.00	D002241	1.50	<0.005		0.001			
91.00	92.50	D002242	1.50	<0.005		0.001			
92.50	94.00	D002243	1.50	<0.005		0.001			
94.00	95.50	D002244	1.50	<0.005		0.001			
95.50	97.00	D002246	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
98.00	103.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP 0.2-0.5 cm, veinules et cheveux de carbonâte, ++calcite, K+, HM+++	97.00	98.50	D002247	1.50	<0.005		0.001
			98.50	100.00	D002248	1.50	<0.005		0.001
			100.00	101.50	D002249	1.50	<0.005		0.001
			101.50	103.00	D002250	1.50	<0.005		0.001
			103.00	104.50	D002251	1.50	<0.005		0.001
			104.50	106.00	D002252	1.50	<0.005		0.001
			106.00	107.50	D002253	1.50	<0.005		0.001
			107.50	109.00	D002254	1.50	<0.005		0.001
			109.00	110.50	D002256	1.50	<0.005		0.001
			110.50	112.00	D002257	1.50	<0.005		0.001
			112.00	113.50	D002258	1.50	<0.005		0.001
			113.50	115.00	D002259	1.50	<0.005		0.001
			115.00	116.00	D002260	1.00	<0.005		0.001
			116.00	117.00	D002261	1.00	0.008		0.008
117.00	118.30	CIS <b>Cisaillement 40°</b>	117.00	118.30	D002262	1.30	<0.005		0.001
			118.30	119.60	D002263	1.30	<0.005		0.001
			119.60	121.00	D002264	1.40	<0.005		0.001
			121.00	122.50	D002266	1.50	<0.005		0.001
			122.50	124.00	D002267	1.50	<0.005		0.001
			124.00	125.50	D002268	1.50	<0.005		0.001
			125.50	127.00	D002269	1.50	<0.005		0.001
			127.00	128.50	D002270	1.50	<0.005		0.001
			128.50	130.00	D002271	1.50	<0.005		0.001
			130.00	131.50	D002272	1.50	0.006		0.006
			131.50	133.00	D002273	1.50	0.119		0.119
			133.00	134.50	D002274	1.50	0.018		0.018
136.00	140.50	CIS <b>Cisaillement 30°</b> cisaillement sub // ac ou 20-30° ac	134.50	136.00	D002276	1.50	<0.005		0.001
			136.00	137.50	D002277	1.50	<0.005		0.001
			137.50	139.00	D002278	1.50	<0.005		0.001
			139.00	140.50	D002279	1.50	<0.005		0.001
			140.50	142.00	D002280	1.50	0.006		0.006
			142.00	143.50	D002281	1.50	<0.005		0.001
			143.50	145.00	D002282	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			145.00	146.50	D002283	1.50	<0.005		0.001
			146.50	148.00	D002284	1.50	<0.005		0.001
			148.00	149.50	D002286	1.50	<0.005		0.001
			149.50	151.00	D002287	1.50	<0.005		0.001
			151.00	152.50	D002288	1.50	<0.005		0.001
			152.50	154.00	D002289	1.50	<0.005		0.001
			154.00	155.50	D002290	1.50	<0.005		0.001
			155.50	157.00	D002291	1.50	<0.005		0.001
			157.00	158.50	D002292	1.50	<0.005		0.001
			158.50	160.00	D002293	1.50	<0.005		0.001
			160.00	161.00	D002294	1.00	<0.005		0.001
161.00	168.50	CIS	161.00	162.50	D002296	1.50	<0.005		0.001
		<b>Cisaillement 20°</b>	162.50	164.00	D002297	1.50	<0.005		0.001
		cisaillent 20-30° ac ou sub // ac	164.00	165.50	D002298	1.50	<0.005		0.001
			165.50	167.00	D002299	1.50	<0.005		0.001
			167.00	168.50	D002300	1.50	<0.005		0.001
			168.50	170.00	D002301	1.50	<0.005		0.001
			170.00	171.50	D002302	1.50	0.693		0.693
171.50	177.90	CIS	171.50	173.00	D002303	1.50	1.305		1.305
		<b>Cisaillement 30°</b>	173.00	174.50	D002304	1.50	0.234		0.234
			174.50	176.00	D002306	1.50	0.203		0.203
			176.00	177.50	D002307	1.50	<0.005		0.001
			177.50	178.80	D002308	1.30	0.014		0.014
			178.80	179.90	D002309	1.10	0.005		0.005
			179.90	181.40	D002310	1.50	<0.005		0.001
			181.40	183.00	D002311	1.60	<0.005		0.001
181.90	183.00	CIS	183.00	184.50	D002312	1.50	<0.005		0.001
		<b>Cisaillement 30°</b>	184.50	186.00	D002313	1.50	<0.005		0.001
			186.00	187.50	D002314	1.50	0.015		0.015
			187.50	189.00	D002316	1.50	<0.005		0.001
			189.00	190.50	D002317	1.50	<0.005		0.001
			190.50	192.00	D002318	1.50	<0.005		0.001
			192.00	193.50	D002319	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
199.50	203.90	CIS Cisaillement 40°	193.50	195.00	D002320	1.50	<0.005		0.001
			195.00	196.50	D002321	1.50	<0.005		0.001
			196.50	198.00	D002322	1.50	<0.005		0.001
			198.00	199.50	D002323	1.50	<0.005		0.001
			199.50	201.00	D002324	1.50	0.014		0.014
			201.00	202.50	D002326	1.50	<0.005		0.001
			202.50	203.90	D002327	1.40	<0.005		0.001
			203.90	205.50	D002328	1.60	<0.005		0.001
			205.50	207.00	D002329	1.50	0.034		0.034
			207.00	208.50	D002330	1.50	0.026		0.026
			208.50	210.00	D002331	1.50	0.030		0.030
			210.00	211.50	D002332	1.50	<0.005		0.001
			211.50	213.00	D002333	1.50	0.005		0.005
			213.00	214.50	D002334	1.50	0.014		0.014
			214.50	216.00	D002336	1.50	<0.005		0.001
			216.00	217.50	D002337	1.50	<0.005		0.001
			217.50	219.00	D002338	1.50	<0.005		0.001
			219.00	220.50	D002339	1.50	<0.005		0.001
			220.50	222.00	D002340	1.50	<0.005		0.001
			222.00	223.50	D002341	1.50	<0.005		0.001
			223.50	225.00	D002342	1.50	0.220		0.220
			225.00	226.50	D002343	1.50	0.174		0.174
			226.50	228.00	D002344	1.50	0.088		0.088
			228.00	229.50	D002346	1.50	0.056		0.056
			229.50	231.00	D002347	1.50	<0.005		0.001
			231.00	232.00	D002348	1.00	<0.005		0.001
			232.00	233.60	D002349	1.60	0.010		0.010
			233.60	235.00	D002350	1.40	<0.005		0.001
			235.00	236.50	D002351	1.50	0.041		0.041
			236.50	238.00	D002352	1.50	0.011		0.011
238.00	239.50	D002353	1.50	<0.005		0.001			
239.50	241.00	D002354	1.50	<0.005		0.001			
241.00	242.50	D002356	1.50	0.006		0.006			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	242.50	244.00	D002357	1.50	<0.005		0.001
	244.00	245.50	D002358	1.50	<0.005		0.001
	245.50	247.00	D002359	1.50	<0.005		0.001
	247.00	248.50	D002360	1.50	<0.005		0.001
	248.50	250.00	D002361	1.50	<0.005		0.001
	250.00	251.50	D002362	1.50	<0.005		0.001
	251.50	253.00	D002363	1.50	<0.005		0.001
	253.00	254.50	D002364	1.50	<0.005		0.001
	254.50	256.00	D002366	1.50	<0.005		0.001
	256.00	257.50	D002367	1.50	<0.005		0.001
	257.50	259.00	D002368	1.50	<0.005		0.001
	259.00	260.50	D002369	1.50	<0.005		0.001
	260.50	262.00	D002370	1.50	0.006		0.006
	262.00	263.50	D002371	1.50	<0.005		0.001
	263.50	265.00	D002372	1.50	0.013		0.013
	265.00	266.50	D002373	1.50	0.005		0.005
	266.50	268.00	D002374	1.50	0.005		0.005
	268.00	269.50	D002376	1.50	<0.005		0.001
	269.50	271.00	D002377	1.50	<0.005		0.001
	271.00	272.50	D002378	1.50	<0.005		0.001
	272.50	274.00	D002379	1.50	0.016		0.016
	274.00	275.50	D002380	1.50	<0.005		0.001
	275.50	277.00	D002381	1.50	<0.005		0.001
	277.00	278.50	D002382	1.50	<0.005		0.001
	278.50	280.00	D002383	1.50	0.058		0.058
	280.00	281.00	D002384	1.00	0.026		0.026
	281.00	282.00	D002386	1.00	0.173		0.173
	282.00	283.00	D002387	1.00	0.016		0.016
	283.00	284.50	D002388	1.50	0.007		0.007
	284.50	286.00	D002389	1.50	0.009		0.009
	286.00	287.50	D002390	1.50	0.023		0.023
	287.50	289.00	D002391	1.50	0.009		0.009
	289.00	290.50	D002392	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			290.50	292.00	D002393	1.50	<0.005		0.001
			292.00	293.50	D002394	1.50	<0.005		0.001
			293.50	295.00	D002396	1.50	<0.005		0.001
			295.00	296.50	D002397	1.50	<0.005		0.001
			296.50	298.00	D002398	1.50	0.008		0.008
			298.00	299.50	D002399	1.50	0.028		0.028
			299.50	301.00	D002400	1.50	0.011		0.011
			301.00	302.00	D002401	1.00	<0.005		0.001
			302.00	303.50	D002402	1.50	<0.005		0.001
			303.50	305.00	D002403	1.50	0.007		0.007
			305.00	306.00	D002404	1.00	0.034		0.034
			306.00	307.20	D002406	1.20	<0.005		0.001
307.20	317.10	BA; MAS <b>Basalte 30°; Roche massive</b> légèrement cisailé, brêchifications localisé et silicifié, vQZ cheve 60° ac, cheveux 40° ac, SR+++, CL+, PY fine	307.20	308.50	D002407	1.30	<0.005		0.001
			308.50	310.00	D002408	1.50	0.033		0.033
			310.00	311.50	D002409	1.50	0.006		0.006
311.50	317.10	CIS <b>Cisaillement 40°</b>	311.50	313.00	D002410	1.50	0.038		0.038
			313.00	314.50	D002411	1.50	0.179		0.179
			314.50	316.00	D002412	1.50	0.392		0.392
			316.00	317.10	D002413	1.10	<0.005		0.001
317.10	321.50	SY; MAS <b>Syénite 40°; Roche massive</b> légèrement cisailé 30-50° ac, cheveux 30° ac, SR+++, CL+++, PY fine diss	317.10	318.50	D002414	1.40	<0.005		0.001
			318.50	320.00	D002416	1.50	0.013		0.013
			320.00	321.50	D002417	1.50	0.005		0.005
321.50	322.80	BA; MAS; AMY <b>Basalte 60°; Roche massive; Amygdalaire</b> altération en calcite et séricite, chloritisation , lentilles de Qz cm, 1VQZ ± 40 cm en fin d'éch, PY fine diss	321.50	322.80	D002418	1.30	0.034		0.034
322.80	366.50	SY; MAS <b>Syénite 30°; Roche massive</b> localement brêchique à sub brêchique, qlq phénocristaux de FP blanchâtre su automorphe, veines, veinules et cheveux de carbonâtes et QZ, séricitatin, chlortisation et hématisation, PY fine irrég diss. DEFONCÉ en fin d' éch	322.80	324.00	D002419	1.20	0.010		0.010
			324.00	325.50	D002420	1.50	0.371		0.371
			325.50	327.00	D002421	1.50	0.036		0.036
			327.00	328.50	D002422	1.50	0.014		0.014
			328.50	330.00	D002423	1.50	0.029		0.029
			330.00	331.50	D002424	1.50	<0.005		0.001
			331.50	333.00	D002426	1.50	0.023		0.023



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			333.00	334.50	D002427	1.50		0.009		0.009
			334.50	335.80	D002428	1.30		<0.005		0.001
			335.80	336.80	D002429	1.00		0.017		0.017
			336.80	337.80	D002430	1.00		0.104		0.104
			337.80	339.00	D002431	1.20		0.468		0.468
			339.00	340.50	D002432	1.50		<0.005		0.001
			340.50	342.00	D002433	1.50		<0.005		0.001
			342.00	343.50	D002434	1.50		<0.005		0.001
			343.50	345.00	D002436	1.50		<0.005		0.001
			345.00	346.50	D002437	1.50		<0.005		0.001
			346.50	348.00	D002438	1.50		<0.005		0.001
			348.00	349.50	D002439	1.50		<0.005		0.001
			349.50	350.50	D002440	1.00		<0.005		0.001
			350.50	352.00	D002441	1.50		<0.005		0.001
			352.00	353.50	D002442	1.50		0.077		0.077
			353.50	355.00	D002443	1.50		0.015		0.015
			355.00	356.00	D002444	1.00		0.017		0.017
			356.00	357.50	D002446	1.50		0.008		0.008
			357.50	359.00	D002447	1.50		<0.005		0.001
			359.00	360.50	D002448	1.50		<0.005		0.001
			360.50	362.00	D002449	1.50		0.046		0.046
			362.00	363.00	D002450	1.00		0.066		0.066
			363.00	364.00	D002451	1.00		0.072		0.072
322.80	331.50	SY; BRC <b>Syénite; Brèche de coulée</b> bréchique à sub bréchique, localement phénocristaux de FP, veinules, veines et cheveux carbonatés, SR++, HM++, CL++, PY fine irrég diss								
364.00	365.70	CIS <b>Cisaillement 40°</b>	364.00	365.50	D002452	1.50		0.020		0.020
			365.50	366.50	D002453	1.00		<0.005		0.001
366.50	366.51	OM <b>Ouverture minière</b> pas de marque évidente de défonçage								

366.51

Fin du sondage

Nombre d'échantillons : 251

Nombre d'échantillons QAQC : 27

Longueur totale échantillonnée : 364.30

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	15.50	D002185	D002184	1.50	<0.005	0.001
27.50	29.00	D002195	A3	1.50	0.593	0.593
40.90	42.50	D002205	D002204	1.60	<0.005	0.001
53.50	55.00	D002215	M1	1.50	<0.005	0.001
67.00	68.50	D002225	D002224	1.50	0.014	0.014
80.50	82.00	D002235	B4	1.50	2.560	2.560
94.00	95.50	D002245	D002244	1.50	<0.005	0.001
107.50	109.00	D002255	M1	1.50	0.007	0.007
119.60	121.00	D002265	D002264	1.40	0.005	0.005
133.00	134.50	D002275	C4	1.50	1.345	1.345
146.50	148.00	D002285	D002284	1.50	<0.005	0.001
160.00	161.00	D002295	M1	1.00	<0.005	0.001
173.00	174.50	D002305	D002304	1.50	0.243	0.243
186.00	187.50	D002315	D2	1.50	0.853	0.853
199.50	201.00	D002325	D002324	1.50	0.012	0.012
213.00	214.50	D002335	M1	1.50	<0.005	0.001
226.50	228.00	D002345	D002344	1.50	0.092	0.092
239.50	241.00	D002355	F2	1.50	8.650	8.550
253.00	254.50	D002365	D002364	1.50	<0.005	0.001
266.50	268.00	D002375	M1	1.50	<0.005	0.001
280.00	281.00	D002385	D002384	1.00	0.033	0.033
292.00	293.50	D002395	G2	1.50	4.040	4.120
305.00	306.00	D002405	D002404	1.00	0.027	0.027
317.10	318.50	D002415	M1	1.40	<0.005	0.001
330.00	331.50	D002425	D002424	1.50	<0.005	0.001
342.00	343.50	D002435	H	1.50	0.976	0.976
355.00	356.00	D002445	D002444	1.00	0.012	0.012

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-136**

Titre minier :

Section :                      630 600

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David Ruhara

Du :                      2010-03-09

Date de description :

Au :                     2010-03-11

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            266.00 m

Est	630 600.1
Nord	5 374 500.3
Élévation	300.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	1.20°	-60.10°	Non
Reflex	5.00	358.80°	-59.90°	Oui
Reflex	8.00	1.20°	-60.10°	Non
Reflex	11.00	3.00°	-60.10°	Non
Reflex	14.00	1.40°	-60.00°	Non
Reflex	17.00	358.90°	-59.90°	Non
Reflex	20.00	359.30°	-59.90°	Non
Reflex	23.00	357.00°	-59.90°	Non
Reflex	26.00	1.30°	-59.90°	Non
Reflex	29.00	1.10°	-59.90°	Non
Reflex	32.00	0.60°	-59.90°	Non
Reflex	35.00	0.10°	-59.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.30°	-59.70°	Non
Reflex	41.00	359.10°	-59.70°	Non
Reflex	44.00	358.80°	-59.80°	Non
Reflex	47.00	0.70°	-59.80°	Non
Reflex	50.00	360.00°	-59.80°	Non
Reflex	53.00	1.10°	-59.80°	Non
Reflex	56.00	1.50°	-59.80°	Non
Reflex	59.00	0.90°	-59.80°	Non
Reflex	62.00	2.10°	-59.80°	Oui
Reflex	65.00	1.50°	-59.80°	Non
Reflex	68.00	0.70°	-59.80°	Non
Reflex	71.00	359.50°	-59.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.60°	-59.60°	Non	Reflex	173.00	1.20°	-59.80°	Non
Reflex	77.00	358.90°	-59.50°	Non	Reflex	176.00	1.50°	-59.70°	Non
Reflex	80.00	1.00°	-59.50°	Non	Reflex	179.00	0.70°	-59.70°	Non
Reflex	83.00	1.90°	-59.50°	Non	Reflex	182.00	2.80°	-59.70°	Oui
Reflex	86.00	1.10°	-59.50°	Non	Reflex	185.00	359.80°	-59.60°	Oui
Reflex	89.00	1.90°	-59.50°	Non	Reflex	188.00	1.60°	-59.60°	Non
Reflex	92.00	2.90°	-59.50°	Non	Reflex	191.00	1.60°	-59.60°	Non
Reflex	95.00	359.60°	-59.50°	Oui	Reflex	194.00	2.30°	-59.60°	Oui
Reflex	98.00	2.40°	-59.50°	Non	Reflex	197.00	1.60°	-59.60°	Non
Reflex	101.00	2.60°	-59.50°	Non	Reflex	200.00	1.40°	-59.50°	Non
Reflex	104.00	354.70°	-59.50°	Oui	Reflex	203.00	1.30°	-59.40°	Non
Reflex	107.00	1.60°	-59.50°	Non	Reflex	206.00	1.60°	-59.50°	Non
Reflex	110.00	2.00°	-59.60°	Non	Reflex	209.00	1.60°	-59.50°	Non
Reflex	113.00	3.30°	-59.60°	Oui	Reflex	212.00	1.50°	-59.40°	Non
Reflex	116.00	1.50°	-59.50°	Non	Reflex	215.00	1.50°	-59.40°	Non
Reflex	119.00	1.20°	-59.60°	Non	Reflex	218.00	1.90°	-59.20°	Non
Reflex	122.00	2.70°	-59.60°	Oui	Reflex	221.00	3.20°	-59.20°	Oui
Reflex	125.00	5.10°	-59.60°	Oui	Reflex	224.00	2.30°	-59.20°	Oui
Reflex	128.00	0.90°	-59.70°	Non	Reflex	227.00	1.60°	-59.20°	Non
Reflex	131.00	3.90°	-59.60°	Non	Reflex	230.00	1.50°	-59.10°	Non
Reflex	134.00	5.40°	-59.70°	Oui	Reflex	233.00	1.40°	-59.00°	Non
Reflex	137.00	2.40°	-59.70°	Non	Reflex	236.00	1.40°	-59.00°	Non
Reflex	140.00	0.40°	-59.70°	Non	Reflex	239.00	1.30°	-58.90°	Non
Reflex	143.00	358.50°	-59.70°	Oui	Reflex	242.00	1.30°	-58.80°	Non
Reflex	146.00	1.20°	-59.80°	Non	Reflex	245.00	1.30°	-58.80°	Non
Reflex	149.00	359.40°	-59.80°	Non	Reflex	248.00	1.30°	-58.80°	Non
Reflex	152.00	359.90°	-59.80°	Non	Reflex	251.00	1.30°	-58.70°	Non
Reflex	155.00	0.90°	-59.80°	Non	Reflex	254.00	1.30°	-58.60°	Non
Reflex	158.00	1.40°	-59.90°	Non	Reflex	257.00	1.30°	-58.60°	Non
Reflex	161.00	1.60°	-59.90°	Non	Reflex	260.00	1.30°	-58.60°	Non
Reflex	164.00	1.60°	-59.90°	Non	Reflex	263.00	1.40°	-58.60°	Non
Reflex	167.00	1.40°	-59.90°	Non	Reflex	266.00	1.60°	-58.50°	Non
Reflex	170.00	1.20°	-59.80°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT						
		<b>Mort-terrain</b>						
2.50	32.20	SY; POR	2.50	4.00	D005932	1.50	0.042	0.042
		<b>Syénite; Porphyrique</b>	4.00	5.50	D005933	1.50	0.041	0.041
		Syénite porphyrique avec de phénocristaux Xmm à rarement Xcm.	5.50	7.00	D005934	1.50	0.043	0.043
			7.00	8.50	D005935	1.50	0.039	0.039
			8.50	10.00	D005936	1.50	0.018	0.018
			10.00	11.50	D005938	1.50	0.024	0.024
			11.50	13.00	D005939	1.50	0.008	0.008
			13.00	14.50	D005940	1.50	0.148	0.148
			14.50	16.00	D005941	1.50	0.056	0.056
			16.00	17.50	D005943	1.50	0.012	0.012
			17.50	19.00	D005944	1.50	0.007	0.007
			19.00	20.50	D005945	1.50	0.006	0.006
			20.50	22.00	D005946	1.50	0.037	0.037
			22.00	23.50	D005947	1.50	<0.005	0.001
			23.50	25.00	D005948	1.50	<0.005	0.001
			25.00	26.50	D005949	1.50	<0.005	0.001
			26.50	28.00	D005950	1.50	<0.005	0.001
			28.00	29.50	D005951	1.50	<0.005	0.001
			29.50	31.00	D005953	1.50	<0.005	0.001
			31.00	32.20	D005954	1.20	<0.005	0.001
32.20	35.20	BA; AMY	32.20	33.50	D005955	1.30	0.005	0.005
		<b>Basalte 25°; Amygdalaire</b>	33.50	35.20	D005956	1.70	0.005	0.005
		Basalte faiblement cisailé avec des amugdules allongés.						
35.20	210.40	SY; POR	35.20	36.50	D005957	1.30	<0.005	0.001
		<b>Syénite 40°; Porphyrique</b>	36.50	38.00	D005958	1.50	<0.005	0.001
		Syénite porphyrique avec phénocristaux Xmm, VCB, tendance AK++.	38.00	39.50	D005959	1.50	<0.005	0.001
			39.50	41.00	D005960	1.50	<0.005	0.001
			41.00	42.50	D005961	1.50	<0.005	0.001
			42.50	44.00	D005963	1.50	<0.005	0.001
			44.00	45.50	D005964	1.50	<0.005	0.001
			45.50	47.00	D005965	1.50	0.007	0.007
			47.00	48.50	D005966	1.50	0.007	0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.50	50.00	D005967	1.50	<0.005		0.001
	50.00	51.50	D005968	1.50	<0.005		0.001
	51.50	53.00	D005969	1.50	<0.005		0.001
	53.00	54.50	D005970	1.50	<0.005		0.001
	54.50	56.00	D005971	1.50	<0.005		0.001
	56.00	57.00	D005973	1.00	<0.005		0.001
	57.00	58.50	D005974	1.50	0.006		0.006
	58.50	60.00	D005975	1.50	<0.005		0.001
	60.00	61.50	D005976	1.50	<0.005		0.001
	61.50	63.00	D005978	1.50	<0.005		0.001
	63.00	64.50	D005979	1.50	<0.005		0.001
	64.50	66.00	D005980	1.50	<0.005		0.001
	66.00	67.00	D005981	1.00	<0.005		0.001
	67.00	68.00	D005983	1.00	<0.005		0.001
	68.00	69.50	D005984	1.50	<0.005		0.001
	69.50	71.00	D005985	1.50	0.009		0.009
	71.00	72.50	D005986	1.50	<0.005		0.001
	72.50	74.00	D005987	1.50	<0.005		0.001
	74.00	75.50	D005988	1.50	<0.005		0.001
	75.50	77.00	D005989	1.50	0.005		0.005
	77.00	78.50	D005990	1.50	<0.005		0.001
	78.50	80.00	D005991	1.50	0.006		0.006
	80.00	81.50	D005993	1.50	<0.005		0.001
	81.50	83.00	D005994	1.50	0.006		0.006
	83.00	84.50	D005995	1.50	<0.005		0.001
	84.50	86.00	D005996	1.50	<0.005		0.001
	86.00	87.50	D005997	1.50	0.007		0.007
	87.50	89.00	D005998	1.50	0.016		0.016
	89.00	90.50	D005999	1.50	0.046		0.046
	90.50	92.00	D006000	1.50	<0.005		0.001
	92.00	93.50	D005001	1.50	0.005		0.005
	93.50	95.00	D005003	1.50	0.019		0.019
	95.00	96.50	D005004	1.50	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	96.50	98.00	D005005	1.50	<0.005		0.001
	98.00	99.50	D005006	1.50	<0.005		0.001
	99.50	101.00	D005007	1.50	<0.005		0.001
	101.00	102.50	D005008	1.50	0.010		0.010
	102.50	104.00	D005009	1.50	0.007		0.007
	104.00	105.50	D005010	1.50	<0.005		0.001
	105.50	107.00	D005011	1.50	<0.005		0.001
	107.00	108.50	D005013	1.50	<0.005		0.001
	108.50	110.00	D005014	1.50	0.008		0.008
	110.00	111.50	D005015	1.50	0.008		0.008
	111.50	113.00	D005016	1.50	<0.005		0.001
	113.00	114.50	D005018	1.50	0.005		0.005
	114.50	116.00	D005019	1.50	<0.005		0.001
	116.00	117.50	D005020	1.50	<0.005		0.001
	117.50	119.00	D005021	1.50	<0.005		0.001
	119.00	120.50	D005023	1.50	0.006		0.006
	120.50	122.00	D005024	1.50	<0.005		0.001
	122.00	123.50	D005025	1.50	0.005		0.005
	123.50	125.00	D005026	1.50	0.006		0.006
	125.00	126.50	D005027	1.50	<0.005		0.001
	126.50	128.00	D005028	1.50	<0.005		0.001
	128.00	129.50	D005029	1.50	<0.005		0.001
	129.50	131.00	D005030	1.50	0.005		0.005
	131.00	132.50	D005031	1.50	0.007		0.007
	132.50	134.00	D005033	1.50	<0.005		0.001
	134.00	135.50	D005034	1.50	<0.005		0.001
	135.50	137.00	D005035	1.50	<0.005		0.001
	137.00	138.50	D005036	1.50	<0.005		0.001
	138.50	140.00	D005037	1.50	<0.005		0.001
	140.00	141.50	D005038	1.50	<0.005		0.001
	141.50	143.00	D005039	1.50	<0.005		0.001
	143.00	144.50	D005040	1.50	0.005		0.005
	144.50	146.00	D005041	1.50	0.010		0.010



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
152.80      154.50      QZVN <b>Veine de Quartz massive</b> Veine de quartz massive avec l'inclusion de CB et les fragments d'éponte (syenite).	146.00	147.50	D005043	1.50	0.005		0.005
	147.50	149.00	D005044	1.50	0.010		0.010
	149.00	150.50	D005045	1.50	0.010		0.010
	150.50	151.70	D005046	1.20	<0.005		0.001
	151.70	152.80	D005047	1.10	0.010		0.010
	152.80	154.50	D005048	1.70	0.084		0.084
	154.50	156.00	D005049	1.50	0.289		0.289
	156.00	157.50	D005050	1.50	0.093		0.093
	157.50	159.00	D005051	1.50	0.202		0.202
	159.00	160.50	D005053	1.50	0.386		0.386
	160.50	162.00	D005054	1.50	0.033		0.033
	162.00	163.50	D005055	1.50	0.006		0.006
	163.50	165.00	D005056	1.50	<0.005		0.001
	165.00	166.50	D005058	1.50	0.005		0.005
	166.50	168.00	D005059	1.50	<0.005		0.001
	168.00	169.50	D005060	1.50	<0.005		0.001
	169.50	171.00	D005061	1.50	<0.005		0.001
	171.00	172.00	D005063	1.00	<0.005		0.001
	172.00	173.00	D005064	1.00	<0.005		0.001
	173.00	174.50	D005065	1.50	0.018		0.018
	174.50	176.00	D005066	1.50	0.007		0.007
	176.00	177.50	D005067	1.50	0.007		0.007
	177.50	179.00	D005068	1.50	<0.005		0.001
	179.00	180.50	D005069	1.50	<0.005		0.001
	180.50	182.00	D005070	1.50	<0.005		0.001
	182.00	183.50	D005071	1.50	0.005		0.005
	183.50	185.00	D005073	1.50	<0.005		0.001
	185.00	186.50	D005074	1.50	<0.005		0.001
	186.50	188.00	D005075	1.50	<0.005		0.001
188.00	189.50	D005076	1.50	0.016		0.016	
189.50	191.00	D005077	1.50	0.047		0.047	
191.00	192.50	D005078	1.50	0.009		0.009	
192.50	194.00	D005079	1.50	0.005		0.005	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
210.40	230.50	PO; POR <b>Porphyre 35°; Porphyrique</b> Porphyre avec phenocristaux Xmm à tendance équigranulaire, PY fine et disséminé et VQ.	194.00	195.50	D005080	1.50	0.024	4.20	0.024
			195.50	197.00	D005081	1.50	0.009		0.009
			197.00	198.50	D005083	1.50	<0.005		0.001
			198.50	200.00	D005084	1.50	0.009		0.009
			200.00	201.50	D005085	1.50	<0.005		0.001
			201.50	203.00	D005086	1.50	0.008		0.008
			203.00	204.50	D005087	1.50	<0.005		0.001
			204.50	206.00	D005088	1.50	<0.005		0.001
			206.00	207.50	D005089	1.50	<0.005		0.001
			207.50	209.00	D005090	1.50	<0.005		0.001
			209.00	210.40	D005091	1.40	0.010		0.010
			210.40	212.00	D005093	1.60	1.600		1.600
			212.00	213.50	D005094	1.50	2.970		2.970
			213.50	215.00	D005095	1.50	4.310		4.200
			215.00	216.50	D005096	1.50	1.485		1.485
			216.50	218.00	D005098	1.50	0.937		0.937
			218.00	219.50	D005099	1.50	1.935		1.935
			219.50	221.00	D005100	1.50	2.210		2.210
			221.00	222.50	D005101	1.50	0.396		0.396
			222.50	224.00	D005103	1.50	1.700		1.700
224.00	225.50	D005104	1.50	1.550	1.550				
225.50	227.00	D005105	1.50	0.710	0.710				
227.00	228.50	D005106	1.50	0.331	0.331				
228.50	229.50	D005107	1.00	0.198	0.198				
229.50	230.50	D005108	1.00	0.079	0.079				
230.50	247.00	BA; AMY; COU <b>Basalte 25°; Amygdalaire; Coussiné</b> Basalte massive ,à grains fins, à amygdalaire.	230.50	232.00	D005109	1.50	0.006	0.006	
			232.00	233.50	D005110	1.50	0.007	0.007	
			233.50	235.00	D005111	1.50	0.005	0.005	
			235.00	236.50	D005113	1.50	0.005	0.005	
			236.50	238.00	D005114	1.50	1.640	1.640	
			238.00	239.50	D005115	1.50	0.485	0.485	
			239.50	241.00	D005116	1.50	0.009	0.009	
			241.00	242.50	D005117	1.50	1.395	1.395	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
247.00	260.00	TU; FIN; GRO <b>Tuf à cendre/lapillis 35°; Grains fins; Grains grossiers</b> Tuf à cendre (fins) et lapillis .	242.50	244.00	D005118	1.50	0.013		0.013
			244.00	245.50	D005119	1.50	0.071		0.071
			245.50	247.00	D005120	1.50	0.006		0.006
			247.00	248.50	D005121	1.50	<0.005		0.001
			248.50	250.00	D005123	1.50	<0.005		0.001
			250.00	251.50	D005124	1.50	<0.005		0.001
			251.50	253.00	D005125	1.50	<0.005		0.001
			253.00	254.50	D005126	1.50	<0.005		0.001
			254.50	256.00	D005127	1.50	<0.005		0.001
			256.00	257.50	D005128	1.50	<0.005		0.001
			257.50	259.00	D005129	1.50	<0.005		0.001
			259.00	260.00	D005130	1.00	<0.005		0.001
			260.00	266.00	BA; AMY <b>Basalte 45°; Amygdalaire</b> Basalte massive à grains fins avec des amugdules.	260.00	261.50	D005131	1.50
261.50	263.00	D005133				1.50	<0.005		0.001
263.00	264.50	D005134				1.50	<0.005		0.001
264.50	266.00	D005135				1.50	<0.005		0.001
266.00	<b>Fin du sondage</b> Nombre d'échantillons : 179 Nombre d'échantillons QAQC : 25 Longueur totale échantillonnée : 263.50								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
8.50	10.00	D005937	M1	1.50	<0.005	0.001
14.50	16.00	D005942	A3	1.50	0.586	0.586
28.00	29.50	D005952	D005951	1.50	<0.005	0.001
41.00	42.50	D005962	H	1.50	0.960	0.960
54.50	56.00	D005972	D005971	1.50	<0.005	0.001
60.00	61.50	D005977	M1	1.50	<0.005	0.001
66.00	67.00	D005982	D2	1.00	0.877	0.877
78.50	80.00	D005992	D005991	1.50	<0.005	0.001
92.00	93.50	D005002	B4	1.50	2.610	2.610
105.50	107.00	D005012	D005011	1.50	<0.005	0.001
111.50	113.00	D005017	M1	1.50	<0.005	0.001
117.50	119.00	D005022	F2	1.50	8.670	8.540
131.00	132.50	D005032	D005031	1.50	0.008	0.008
144.50	146.00	D005042	H	1.50	0.989	0.989
157.50	159.00	D005052	D005051	1.50	0.264	0.264
163.50	165.00	D005057	M1	1.50	<0.005	0.001
169.50	171.00	D005062	D2	1.50	0.861	0.861
182.00	183.50	D005072	D005071	1.50	0.005	0.005
195.50	197.00	D005082	A3	1.50	0.646	0.646
209.00	210.40	D005092	D005091	1.40	0.008	0.008
215.00	216.50	D005097	M1	1.50	0.010	0.010
221.00	222.50	D005102	G2	1.50	4.280	4.060
233.50	235.00	D005112	D005111	1.50	0.005	0.005
247.00	248.50	D005122	C4	1.50	1.365	1.365
260.00	261.50	D005132	D005131	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-137**

Titre minier :

Section :                      630 000

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    Guy Gbaguidi

Lot :

Du :                              2010-03-12

Date de description :

Au :                              2010-03-15

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -59.00°  
 Longueur :                    235.80 m

Est	630 000.0
Nord	5 374 400.8
Élévation	281.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	351.00°	-59.00°	Oui
Reflex	11.00	4.80°	-57.90°	Oui
Reflex	14.00	352.60°	-57.40°	Oui
Reflex	17.00	338.40°	-57.40°	Oui
Reflex	20.00	358.50°	-57.80°	Oui
Reflex	23.00	6.80°	-57.70°	Oui
Reflex	26.00	2.70°	-57.50°	Non
Reflex	29.00	3.10°	-57.50°	Non
Reflex	32.00	3.40°	-57.50°	Non
Reflex	35.00	2.50°	-57.40°	Non
Reflex	38.00	2.50°	-57.40°	Non
Reflex	41.00	2.80°	-57.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	2.90°	-57.30°	Non
Reflex	47.00	3.00°	-57.20°	Non
Reflex	50.00	2.90°	-57.10°	Non
Reflex	53.00	2.90°	-57.20°	Non
Reflex	56.00	346.20°	-57.20°	Oui
Reflex	59.00	4.60°	-57.20°	Oui
Reflex	62.00	2.40°	-56.90°	Non
Reflex	65.00	2.70°	-56.90°	Non
Reflex	68.00	2.70°	-56.90°	Non
Reflex	71.00	4.20°	-57.00°	Oui
Reflex	74.00	2.80°	-56.80°	Non
Reflex	77.00	2.70°	-56.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Oui

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	2.20°	-56.70°	Non	Reflex	179.00	2.60°	-54.90°	Non
Reflex	83.00	2.00°	-56.60°	Non	Reflex	182.00	2.40°	-54.90°	Non
Reflex	86.00	2.30°	-56.80°	Non	Reflex	185.00	2.10°	-54.90°	Non
Reflex	89.00	2.10°	-56.90°	Non	Reflex	188.00	2.40°	-54.60°	Non
Reflex	92.00	2.30°	-56.70°	Non	Reflex	191.00	2.10°	-54.70°	Non
Reflex	95.00	2.00°	-56.90°	Non	Reflex	194.00	1.80°	-54.40°	Non
Reflex	98.00	2.50°	-56.60°	Non	Reflex	197.00	2.30°	-54.20°	Non
Reflex	101.00	2.40°	-56.70°	Non	Reflex	200.00	2.20°	-53.90°	Non
Reflex	104.00	2.40°	-56.70°	Non	Reflex	203.00	1.60°	-53.90°	Non
Reflex	107.00	2.60°	-56.70°	Non	Reflex	206.00	1.90°	-53.50°	Non
Reflex	110.00	2.40°	-56.60°	Non	Reflex	209.00	1.60°	-53.20°	Non
Reflex	113.00	2.70°	-56.60°	Non	Reflex	212.00	1.50°	-53.00°	Non
Reflex	116.00	2.10°	-56.60°	Non	Reflex	215.00	1.50°	-53.00°	Non
Reflex	119.00	2.50°	-56.60°	Non	Reflex	218.00	1.50°	-52.90°	Non
Reflex	122.00	2.50°	-56.60°	Non	Reflex	221.00	1.30°	-53.10°	Non
Reflex	125.00	2.20°	-56.70°	Non	Reflex	224.00	1.80°	-52.80°	Non
Reflex	128.00	3.00°	-56.40°	Non	Reflex	227.00	1.40°	-52.60°	Non
Reflex	131.00	3.00°	-56.40°	Non	Reflex	230.00	1.60°	-52.60°	Non
Reflex	134.00	2.70°	-56.40°	Non	Reflex	233.00	1.90°	-52.60°	Non
Reflex	137.00	2.70°	-56.40°	Non	Reflex	235.80	1.90°	-52.70°	Non
Reflex	140.00	2.90°	-56.20°	Non					
Reflex	143.00	2.60°	-56.40°	Non					
Reflex	146.00	2.50°	-56.20°	Non					
Reflex	149.00	2.40°	-56.30°	Non					
Reflex	152.00	2.40°	-55.80°	Non					
Reflex	155.00	2.40°	-56.00°	Non					
Reflex	158.00	2.40°	-55.80°	Non					
Reflex	161.00	2.60°	-56.00°	Non					
Reflex	164.00	2.20°	-55.60°	Non					
Reflex	167.00	2.50°	-55.50°	Non					
Reflex	170.00	2.80°	-55.40°	Non					
Reflex	173.00	2.60°	-55.20°	Non					
Reflex	176.00	2.50°	-55.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	19.60	MT <b>Mort-terrain</b> Mort-Terrain						
19.60	34.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique carbonaté.	19.60	21.00	D010165	1.40	0.005	0.005
			21.00	22.50	D010166	1.50	0.005	0.005
			22.50	24.00	D010167	1.50	<0.005	0.001
			24.00	25.50	D010168	1.50	0.056	0.056
			25.50	27.00	D010169	1.50	0.043	0.043
			27.00	28.50	D010170	1.50	0.048	0.048
			28.50	30.00	D010171	1.50	0.046	0.046
			30.00	31.50	D010172	1.50	0.005	0.005
			31.50	33.00	D010173	1.50	0.007	0.007
			33.00	34.00	D010174	1.00	1.110	1.110
34.00	53.50	PO <b>Porphyre</b> Porphyre silicifié	34.00	35.50	D010176	1.50	1.350	1.350
			35.50	37.00	D010177	1.50	0.739	0.739
			37.00	38.50	D010178	1.50	2.510	2.510
			38.50	40.00	D010179	1.50	2.400	2.400
			40.00	41.50	D010180	1.50	1.205	1.205
			41.50	43.00	D010181	1.50	3.680	3.54
			43.00	44.50	D010182	1.50	4.600	4.61
			44.50	46.00	D010183	1.50	3.020	3.08
			46.00	47.50	D010184	1.50	1.715	1.715
			47.50	49.00	D010186	1.50	1.950	1.950
			49.00	50.50	D010187	1.50	3.360	3.47
			50.50	52.00	D010188	1.50	0.534	0.534
			52.00	53.50	D010189	1.50	0.805	0.805
53.50	57.40	BA; BRC <b>Basalte; Brèche de coulée</b> Induré, bréchique, localement xénolithes de cb.	53.50	55.00	D010190	1.50	0.424	0.424
			55.00	56.00	D010191	1.00	0.007	0.007
			56.00	57.40	D010192	1.40	0.043	0.043
57.40	235.80	BA <b>Basalte</b> massive à gf, séricitisé, fortement carbonaté	57.40	59.00	D010193	1.60	0.005	0.005
			59.00	60.50	D010194	1.50	<0.005	0.001
			60.50	62.00	D010196	1.50	0.006	0.006
			62.00	63.50	D010197	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	63.50	65.00	D010198	1.50	0.005		0.005
	65.00	66.50	D010199	1.50	0.005		0.005
	66.50	68.00	D010200	1.50	<0.005		0.001
	68.00	69.50	D010201	1.50	0.005		0.005
	69.50	71.00	D010202	1.50	<0.005		0.001
	71.00	72.50	D010203	1.50	<0.005		0.001
	72.50	74.00	D010204	1.50	0.005		0.005
	74.00	75.50	D010206	1.50	<0.005		0.001
	75.50	77.00	D010207	1.50	<0.005		0.001
	77.00	78.50	D010208	1.50	<0.005		0.001
	78.50	80.00	D010209	1.50	<0.005		0.001
	80.00	81.50	D010210	1.50	<0.005		0.001
	81.50	83.00	D010211	1.50	<0.005		0.001
	83.00	84.50	D010212	1.50	<0.005		0.001
	84.50	86.00	D010213	1.50	<0.005		0.001
	86.00	87.50	D010214	1.50	0.005		0.005
	87.50	89.00	D010216	1.50	0.006		0.006
	89.00	90.50	D010217	1.50	0.006		0.006
	90.50	92.00	D010218	1.50	0.006		0.006
	92.00	93.50	D010219	1.50	0.007		0.007
	93.50	95.00	D010220	1.50	0.016		0.016
	95.00	96.50	D010221	1.50	0.005		0.005
	96.50	98.00	D010222	1.50	0.005		0.005
	98.00	99.50	D010223	1.50	0.006		0.006
	99.50	101.00	D010224	1.50	0.005		0.005
	101.00	102.50	D010226	1.50	0.009		0.009
	102.50	104.00	D010227	1.50	0.007		0.007
	104.00	105.50	D010228	1.50	<0.005		0.001
	105.50	107.00	D010229	1.50	0.006		0.006
	107.00	108.50	D010230	1.50	0.006		0.006
	108.50	110.00	D010231	1.50	0.006		0.006
	110.00	111.50	D010232	1.50	<0.005		0.001
	111.50	113.00	D010233	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
115.60	120.00	GA <b>Gabbro</b> Massive à gf, induré, magnétique, carbonaté, traces de py.	113.00	114.50	D010234	1.50	<0.005		0.001
			114.50	115.60	D010236	1.10	<0.005		0.001
			115.60	117.00	D010237	1.40	0.005		0.005
			117.00	118.30	D010238	1.30	<0.005		0.001
			118.30	120.00	D010239	1.70	0.158		0.158
			120.00	121.50	D010240	1.50	<0.005		0.001
			121.50	123.00	D010241	1.50	0.005		0.005
			123.00	124.50	D010242	1.50	0.005		0.005
			124.50	126.00	D010243	1.50	<0.005		0.001
			126.00	127.50	D010244	1.50	<0.005		0.001
			127.50	129.00	D010246	1.50	<0.005		0.001
			129.00	130.50	D010247	1.50	<0.005		0.001
			130.50	132.00	D010248	1.50	<0.005		0.001
			132.00	133.50	D010249	1.50	<0.005		0.001
			133.50	135.00	D010250	1.50	<0.005		0.001
			135.00	136.50	D010251	1.50	<0.005		0.001
			136.50	138.00	D010252	1.50	<0.005		0.001
			138.00	139.00	D010253	1.00	0.006		0.006
			139.00	140.50	D010254	1.50	0.005		0.005
			140.50	142.00	D010256	1.50	0.006		0.006
142.00	143.50	D010257	1.50	0.005		0.005			
143.50	145.00	D010258	1.50	0.005		0.005			
145.00	146.50	D010259	1.50	0.011		0.011			
146.50	148.00	D010260	1.50	0.005		0.005			
148.00	149.00	D010261	1.00	0.009		0.009			
149.00	150.50	D010262	1.50	0.006		0.006			
150.50	152.00	D010263	1.50	0.005		0.005			
152.00	153.50	D010264	1.50	0.560		0.560			
153.50	155.00	D010266	1.50	0.011		0.011			
155.00	156.50	D010267	1.50	0.007		0.007			
156.50	158.00	D010268	1.50	0.009		0.009			
158.00	159.50	D010269	1.50	0.013		0.013			
159.50	161.00	D010270	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	161.00	162.50	D010271	1.50	0.007		0.007
	162.50	164.00	D010272	1.50	0.014		0.014
	164.00	165.50	D010273	1.50	0.008		0.008
	165.50	167.00	D010274	1.50	0.007		0.007
	167.00	168.50	D010276	1.50	0.008		0.008
	168.50	170.00	D010277	1.50	0.005		0.005
	170.00	171.50	D010278	1.50	<0.005		0.001
	171.50	173.00	D010279	1.50	<0.005		0.001
	173.00	174.50	D010280	1.50	0.007		0.007
	174.50	176.00	D010281	1.50	<0.005		0.001
	176.00	177.50	D010282	1.50	<0.005		0.001
	177.50	179.00	D010283	1.50	0.006		0.006
	179.00	180.50	D010284	1.50	<0.005		0.001
	180.50	182.00	D010286	1.50	<0.005		0.001
	182.00	183.50	D010287	1.50	<0.005		0.001
	183.50	185.00	D010288	1.50	<0.005		0.001
	185.00	186.50	D010289	1.50	<0.005		0.001
	186.50	188.00	D010290	1.50	<0.005		0.001
	188.00	189.50	D010291	1.50	<0.005		0.001
	189.50	191.00	D010292	1.50	<0.005		0.001
	191.00	192.50	D010293	1.50	0.005		0.005
	192.50	194.00	D010294	1.50	<0.005		0.001
	194.00	195.50	D010296	1.50	<0.005		0.001
	195.50	197.00	D010297	1.50	0.005		0.005
	197.00	198.50	D010298	1.50	0.506		0.506
	198.50	200.00	D010299	1.50	0.866		0.866
	200.00	201.50	D010300	1.50	0.047		0.047
	201.50	203.00	D010301	1.50	0.005		0.005
	203.00	204.50	D010302	1.50	0.005		0.005
	204.50	206.00	D010303	1.50	<0.005		0.001
	206.00	207.50	D010304	1.50	0.005		0.005
	207.50	209.00	D010306	1.50	0.005		0.005
	209.00	210.50	D010307	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	210.50	212.00	D010308	1.50	<0.005		0.001
	212.00	213.50	D010309	1.50	<0.005		0.001
	213.50	215.00	D010310	1.50	<0.005		0.001
	215.00	216.50	D010311	1.50	0.007		0.007
	216.50	218.00	D010312	1.50	<0.005		0.001
	218.00	219.50	D010313	1.50	0.005		0.005
	219.50	221.00	D010314	1.50	0.006		0.006
	221.00	222.50	D010316	1.50	0.006		0.006
	222.50	224.00	D010317	1.50	0.006		0.006
	224.00	225.50	D010318	1.50	0.007		0.007
	225.50	227.00	D010319	1.50	0.007		0.007
	227.00	228.50	D010320	1.50	0.007		0.007
	228.50	230.00	D010321	1.50	0.006		0.006
	230.00	231.50	D010322	1.50	0.006		0.006
	231.50	233.00	D010323	1.50	0.006		0.006
	233.00	234.50	D010324	1.50	0.007		0.007
	234.50	235.80	D010326	1.30	0.006		0.006
235.80	Fin du sondage Nombre d'échantillons : 146 Nombre d'échantillons QAQC : 16 Longueur totale échantillonnée : 216.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
33.00	34.00	D010175	D010174	1.00	1.085	1.085
46.00	47.50	D010185	A3	1.50	0.600	0.600
59.00	60.50	D010195	D010194	1.50	<0.005	0.001
72.50	74.00	D010205	M1	1.50	<0.005	0.001
86.00	87.50	D010215	D010214	1.50	0.005	0.005
99.50	101.00	D010225	B4	1.50	2.670	2.670
113.00	114.50	D010235	D010234	1.50	<0.005	0.001
126.00	127.50	D010245	M1	1.50	<0.005	0.001
139.00	140.50	D010255	D010254	1.50	0.005	0.005
152.00	153.50	D010265	C3	1.50	1.410	1.410
165.50	167.00	D010275	D010274	1.50	0.007	0.007
179.00	180.50	D010285	M1	1.50	<0.005	0.001
192.50	194.00	D010295	D010294	1.50	<0.005	0.001
206.00	207.50	D010305	D2	1.50	0.892	0.892
219.50	221.00	D010315	D010314	1.50	0.006	0.006
233.00	234.50	D010325	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-138**

Titre minier :

Section :                      630700

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          Gilles. KAMTA

Du :                      2010-03-21

Date de description :

Au :                     2010-03-24

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            437.20 m

Est	630 700.1
Nord	5 374 450.6
Élévation	308.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	359.30°	-59.60°	Oui
Reflex	5.00	358.10°	-59.80°	Non
Reflex	8.00	0.60°	-59.80°	Non
Reflex	11.00	359.90°	-60.00°	Non
Reflex	14.00	1.00°	-59.90°	Non
Reflex	17.00	0.30°	-59.90°	Non
Reflex	20.00	0.80°	-59.90°	Non
Reflex	23.00	1.40°	-60.00°	Non
Reflex	26.00	1.90°	-60.00°	Non
Reflex	29.00	1.80°	-60.00°	Non
Reflex	32.00	3.40°	-60.10°	Oui
Reflex	35.00	2.30°	-60.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.40°	-60.30°	Non
Reflex	41.00	358.30°	-60.30°	Non
Reflex	44.00	1.20°	-60.40°	Non
Reflex	47.00	2.40°	-60.40°	Oui
Reflex	50.00	358.80°	-60.40°	Non
Reflex	53.00	359.70°	-60.40°	Non
Reflex	56.00	358.80°	-60.40°	Non
Reflex	59.00	1.50°	-60.50°	Non
Reflex	62.00	3.10°	-60.50°	Non
Reflex	65.00	3.80°	-60.40°	Non
Reflex	68.00	3.30°	-60.30°	Non
Reflex	71.00	2.00°	-60.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.80°	-60.40°	Non	Reflex	173.00	5.70°	-60.40°	Non
Reflex	77.00	2.00°	-60.30°	Non	Reflex	176.00	7.20°	-60.30°	Non
Reflex	80.00	2.50°	-60.40°	Non	Reflex	179.00	5.60°	-60.30°	Oui
Reflex	83.00	2.70°	-60.30°	Non	Reflex	182.00	6.20°	-60.20°	Non
Reflex	86.00	2.90°	-60.30°	Non	Reflex	185.00	6.50°	-60.20°	Non
Reflex	89.00	3.00°	-60.30°	Non	Reflex	188.00	7.80°	-60.10°	Non
Reflex	92.00	4.10°	-60.40°	Oui	Reflex	191.00	358.30°	-60.00°	Oui
Reflex	95.00	3.00°	-60.40°	Non	Reflex	194.00	6.70°	-60.10°	Non
Reflex	98.00	2.90°	-60.40°	Non	Reflex	197.00	7.90°	-60.10°	Non
Reflex	101.00	2.90°	-60.30°	Non	Reflex	200.00	7.40°	-60.10°	Non
Reflex	104.00	2.40°	-60.30°	Non	Reflex	203.00	1.80°	-60.10°	Oui
Reflex	107.00	2.10°	-60.30°	Non	Reflex	206.00	4.90°	-60.20°	Non
Reflex	110.00	1.90°	-60.30°	Non	Reflex	209.00	7.00°	-60.20°	Non
Reflex	113.00	1.70°	-60.30°	Non	Reflex	212.00	7.50°	-60.20°	Non
Reflex	116.00	2.00°	-60.40°	Non	Reflex	215.00	8.70°	-60.20°	Non
Reflex	119.00	2.20°	-60.40°	Non	Reflex	218.00	3.70°	-60.30°	Oui
Reflex	122.00	2.00°	-60.40°	Non	Reflex	221.00	6.40°	-60.20°	Non
Reflex	125.00	1.40°	-60.30°	Non	Reflex	224.00	12.10°	-60.30°	Oui
Reflex	128.00	1.30°	-60.20°	Non	Reflex	227.00	8.50°	-60.30°	Non
Reflex	131.00	1.60°	-60.30°	Non	Reflex	230.00	9.30°	-60.30°	Non
Reflex	134.00	1.50°	-60.40°	Non	Reflex	233.00	6.20°	-60.30°	Oui
Reflex	137.00	1.70°	-60.40°	Non	Reflex	236.00	8.40°	-60.40°	Non
Reflex	140.00	0.40°	-60.50°	Oui	Reflex	239.00	4.10°	-60.40°	Non
Reflex	143.00	2.00°	-60.50°	Non	Reflex	242.00	4.00°	-60.50°	Non
Reflex	146.00	1.80°	-60.50°	Non	Reflex	245.00	5.10°	-60.50°	Non
Reflex	149.00	2.20°	-60.50°	Non	Reflex	248.00	9.10°	-60.40°	Oui
Reflex	152.00	3.00°	-60.50°	Non	Reflex	251.00	7.30°	-60.40°	Non
Reflex	155.00	3.50°	-60.50°	Non	Reflex	254.00	8.90°	-60.50°	Non
Reflex	158.00	5.40°	-60.50°	Non	Reflex	257.00	6.80°	-60.50°	Non
Reflex	161.00	6.60°	-60.60°	Non	Reflex	260.00	7.40°	-60.50°	Non
Reflex	164.00	7.10°	-60.60°	Non	Reflex	263.00	7.80°	-60.60°	Non
Reflex	167.00	8.10°	-60.60°	Non	Reflex	266.00	7.40°	-60.50°	Non
Reflex	170.00	5.70°	-60.40°	Non	Reflex	269.00	6.70°	-60.50°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	6.50°	-60.50°	Non	Reflex	371.00	9.10°	-59.00°	Non
Reflex	275.00	6.90°	-60.60°	Non	Reflex	374.00	9.10°	-58.90°	Non
Reflex	278.00	6.70°	-60.60°	Non	Reflex	377.00	9.10°	-58.80°	Non
Reflex	281.00	7.00°	-60.70°	Non	Reflex	380.00	9.10°	-58.90°	Non
Reflex	284.00	7.00°	-60.70°	Non	Reflex	383.00	9.30°	-58.90°	Non
Reflex	287.00	7.10°	-60.70°	Non	Reflex	386.00	9.30°	-58.80°	Non
Reflex	290.00	7.30°	-60.70°	Non	Reflex	389.00	9.40°	-58.80°	Non
Reflex	293.00	7.60°	-60.70°	Non	Reflex	392.00	9.50°	-58.80°	Non
Reflex	296.00	7.90°	-60.70°	Non	Reflex	395.00	9.70°	-58.70°	Non
Reflex	299.00	7.90°	-60.70°	Non	Reflex	398.00	9.70°	-58.60°	Non
Reflex	302.00	8.00°	-60.80°	Non	Reflex	401.00	9.90°	-58.60°	Non
Reflex	305.00	8.10°	-60.80°	Non	Reflex	404.00	10.00°	-58.40°	Non
Reflex	308.00	8.20°	-60.80°	Non	Reflex	407.00	10.10°	-58.30°	Non
Reflex	311.00	8.30°	-60.70°	Non	Reflex	410.00	10.20°	-58.30°	Non
Reflex	314.00	8.30°	-60.60°	Non	Reflex	413.00	10.40°	-58.20°	Non
Reflex	317.00	8.40°	-60.60°	Non	Reflex	416.00	10.60°	-58.10°	Non
Reflex	320.00	8.50°	-60.60°	Non	Reflex	419.00	10.70°	-58.00°	Non
Reflex	323.00	8.60°	-60.50°	Non	Reflex	422.00	10.90°	-58.00°	Non
Reflex	326.00	8.80°	-60.50°	Non	Reflex	425.00	11.00°	-57.90°	Non
Reflex	329.00	8.70°	-60.40°	Non	Reflex	428.00	11.10°	-57.80°	Non
Reflex	332.00	8.50°	-60.30°	Non	Reflex	431.00	11.40°	-57.70°	Non
Reflex	335.00	8.70°	-60.20°	Non	Reflex	434.00	11.50°	-57.60°	Non
Reflex	338.00	8.90°	-60.20°	Non					
Reflex	341.00	8.90°	-60.10°	Non					
Reflex	344.00	8.80°	-60.00°	Non					
Reflex	347.00	8.80°	-59.80°	Non					
Reflex	350.00	9.10°	-59.70°	Non					
Reflex	353.00	9.00°	-59.60°	Non					
Reflex	356.00	9.70°	-60.40°	Non					
Reflex	359.00	9.00°	-59.50°	Non					
Reflex	362.00	9.00°	-59.40°	Non					
Reflex	365.00	9.10°	-59.20°	Non					
Reflex	368.00	9.00°	-59.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.60	MT						
		<b>Mort-terrain</b>						
2.60	142.30	SY; MAS; MTY; FIN; MAG	2.60	4.00	D001397	1.40	<0.005	0.001
		<b>Syénite; Roche massive; Grains moyens; Grains fins;</b>	4.00	5.50	D001398	1.50	<0.005	0.001
		<b>Magnétique</b>	5.50	7.00	D001399	1.50	<0.005	0.001
		altération potassique, altération en calcite, hématisation, veines de QZ	7.00	8.50	D001400	1.50	<0.005	0.001
		carbonaté, veinules et cheveux de carbonatés, séricite, oxydes de	8.50	10.00	D001401	1.50	0.008	0.008
		carbonates, chlorite, PY fine, arsénopyrite fine	10.00	11.50	D001402	1.50	<0.005	0.001
			11.50	13.00	D001403	1.50	<0.005	0.001
			13.00	14.50	D001404	1.50	0.007	0.007
			14.50	16.00	D001405	1.50	<0.005	0.001
			16.00	17.50	D001407	1.50	<0.005	0.001
			17.50	19.00	D001408	1.50	0.005	0.005
			19.00	20.50	D001409	1.50	<0.005	0.001
			20.50	22.00	D001410	1.50	0.006	0.006
			22.00	23.50	D001411	1.50	<0.005	0.001
			23.50	25.00	D001412	1.50	<0.005	0.001
			25.00	26.50	D001413	1.50	<0.005	0.001
			26.50	28.00	D001414	1.50	<0.005	0.001
			28.00	29.50	D001415	1.50	<0.005	0.001
			29.50	31.00	D001417	1.50	<0.005	0.001
			31.00	32.50	D001418	1.50	<0.005	0.001
			32.50	34.00	D001419	1.50	<0.005	0.001
			34.00	35.50	D001420	1.50	<0.005	0.001
			35.50	37.00	D001421	1.50	0.011	0.011
			37.00	38.50	D001422	1.50	<0.005	0.001
			38.50	40.00	D001423	1.50	0.008	0.008
			40.00	41.50	D001424	1.50	0.010	0.010
			41.50	43.00	D001425	1.50	<0.005	0.001
			43.00	44.50	D001427	1.50	<0.005	0.001
			44.50	46.00	D001428	1.50	<0.005	0.001
			46.00	47.50	D001429	1.50	<0.005	0.001
			47.50	49.00	D001430	1.50	<0.005	0.001
			49.00	50.00	D001431	1.00	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.00	D001432	1.00	<0.005		0.001
	51.00	52.50	D001433	1.50	<0.005		0.001
	52.50	54.00	D001434	1.50	<0.005		0.001
	54.00	55.50	D001435	1.50	<0.005		0.001
	55.50	57.00	D001437	1.50	<0.005		0.001
	57.00	58.50	D001438	1.50	<0.005		0.001
	58.50	60.00	D001439	1.50	<0.005		0.001
	60.00	61.50	D001440	1.50	<0.005		0.001
	61.50	63.00	D001441	1.50	<0.005		0.001
	63.00	64.00	D001442	1.00	0.008		0.008
	64.00	65.00	D001443	1.00	<0.005		0.001
	65.00	66.50	D001444	1.50	<0.005		0.001
	66.50	68.00	D001445	1.50	<0.005		0.001
	68.00	69.50	D001447	1.50	<0.005		0.001
	69.50	71.00	D001448	1.50	<0.005		0.001
	71.00	72.50	D001449	1.50	0.010		0.010
	72.50	74.00	D001450	1.50	0.006		0.006
	74.00	75.50	D001451	1.50	<0.005		0.001
	75.50	77.00	D001452	1.50	0.013		0.013
	77.00	78.50	D001453	1.50	<0.005		0.001
	78.50	80.00	D001454	1.50	<0.005		0.001
	80.00	81.50	D001455	1.50	<0.005		0.001
	81.50	83.00	D001457	1.50	<0.005		0.001
	83.00	84.50	D001458	1.50	<0.005		0.001
	84.50	86.00	D001459	1.50	<0.005		0.001
	86.00	87.50	D001460	1.50	<0.005		0.001
	87.50	89.00	D001461	1.50	0.007		0.007
	89.00	90.50	D001462	1.50	0.011		0.011
	90.50	92.00	D001463	1.50	<0.005		0.001
	92.00	93.50	D001464	1.50	<0.005		0.001
	93.50	95.00	D001465	1.50	<0.005		0.001
	95.00	96.50	D001467	1.50	0.025		0.025
	96.50	98.00	D001468	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
2.60	51.00	SY; MOY; FIN; POR <b>Syénite; Grains moyens; Grains fins; Porphyrique</b> phénocristaux 0.2-1 cm, altération potassique, veines de de carbonâtes, localement altéré en calcite, localement magnétique, hématisation légère séricitisation	98.00	99.00	D001469	1.00	0.037		0.037
			99.00	100.00	D001470	1.00	0.209		0.209
			100.00	101.50	D001471	1.50	0.038		0.038
			101.50	103.00	D001472	1.50	0.013		0.013
			103.00	104.50	D001473	1.50	<0.005		0.001
			104.50	106.00	D001474	1.50	0.023		0.023
			106.00	110.50					
106.00	110.50	SY; BRI <b>Syénite; Brèche intrusive</b> brêchifications fluidales par le QZ et calcite, qlq fragments anguleux, localement cisailé, altération séricite, veines de calcite ± 50 cm, veines de QZ hématisé, PY automorphe et fine diss	106.00	107.50	D001475	1.50	0.571		0.571
			107.50	109.00	D001477	1.50	2.240		2.240
			109.00	110.50	D001478	1.50	1.025		1.025
			110.50	112.00	D001479	1.50	1.405		1.405
			112.00	113.00	D001480	1.00	0.483		0.483
			113.00	114.00	D001481	1.00	0.327		0.327
114.00	120.00	SY; POR <b>Syénite; Porphyrique</b> texture pseudo trachitique ( phénocristaux grossiers et automorphe de FP 0.3-2 cm allongés localement orientés 30-40° ac), localement brêchique, séricitisation, légèrement potassique, PY fine diss	114.00	115.50	D001482	1.50	0.253		0.253
			115.50	117.00	D001483	1.50	0.051		0.051
			117.00	118.50	D001484	1.50	0.097		0.097
			118.50	120.00	D001485	1.50	0.211		0.211
			120.00	121.50	D001487	1.50	0.310		0.310
			121.50	123.00	D001488	1.50	0.006		0.006
			123.00	124.00	D001489	1.00	0.007		0.007
124.00	125.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux sub arrondi 0.3 -2 cm localement orienté et/ ou biotitique, vCC 30-40° ac, cheveux 30° ac, lentilles de QZ carbonaté, SR++, CL+, EP+, PY diss							
124.00	125.00	CIS <b>Cisaillement 30°</b>	124.00	125.00	D001490	1.00	0.034		0.034
			125.00	126.50	D001491	1.50	<0.005		0.001
			126.50	128.00	D001492	1.50	0.029		0.029
			128.00	129.50	D001493	1.50	0.013		0.013
			129.50	131.00	D001494	1.50	0.006		0.006
			131.00	132.50	D001495	1.50	0.054		0.054

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
142.30	145.30	BA; AMY <b>Basalte andésitique; Amygdalaire</b> intrusif andésitique, cisailé, 40-50° ac, amygdalaire, localement // cisaillement séricitisation, chloritisation, épidotisation, PY fine irrég diss	132.50	134.00	D001497	1.50	0.007		0.007
			134.00	135.50	D001498	1.50	0.094		0.094
			135.50	137.00	D001499	1.50	0.028		0.028
			137.00	138.50	D001500	1.50	<0.005		0.001
			138.50	140.00	D001501	1.50	<0.005		0.001
			140.00	141.20	D001502	1.20	<0.005		0.001
			141.20	142.30	D001503	1.10	0.039		0.039
142.30	145.30	CIS <b>Cisaillement 45°</b>	142.30	143.70	D001504	1.40	0.027		0.027
142.30	145.30	CIS <b>Cisaillement 45°</b>	143.70	145.30	D001505	1.60	0.043		0.043
145.30	375.20	SY; MAS; FIN; MAG <b>Syénite; Roche massive; Grains fins; Magnétique</b> altération potassique et en calcite, qlq phénocristaux de FP 0.2-0.6 cm diss, localement altération en silice avec sub bréchification, Veines de QZ carbonatés, veinules et cheveux carbonatés, BO+, SR+, PY automorphe et fine irrég diss	145.30	146.50	D001507	1.20	0.098		0.098
			146.50	148.00	D001508	1.50	<0.005		0.001
			148.00	149.50	D001509	1.50	0.007		0.007
			149.50	151.00	D001510	1.50	<0.005		0.001
			151.00	152.50	D001511	1.50	<0.005		0.001
			152.50	154.00	D001512	1.50	<0.005		0.001
			154.00	155.50	D001513	1.50	0.005		0.005
			155.50	157.00	D001514	1.50	0.005		0.005
			157.00	158.50	D001515	1.50	<0.005		0.001
			158.50	160.00	D001517	1.50	<0.005		0.001
			160.00	161.50	D001518	1.50	<0.005		0.001
163.00	168.30	SY; POR <b>Syénite; Porphyrique</b> altération potassique, phénocristaux de FP automorphe 0.2-2 cm, localement trachytique( orienté 40-60° ac), SR+, veines de QTZ carbonaté, PY irrégis	161.50	163.00	D001519	1.50	<0.005		0.001
			163.00	164.50	D001520	1.50	0.008		0.008
			164.50	166.00	D001521	1.50	0.008		0.008
			166.00	167.30	D001522	1.30	0.017		0.017
			167.30	168.30	D001523	1.00	<0.005		0.001
			168.30	169.50	D001524	1.20	<0.005		0.001
			169.50	171.00	D001525	1.50	0.007		0.007
			171.00	172.50	D001527	1.50	0.011		0.011
172.50	174.00	D001528	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	174.00	175.50	D001529	1.50	0.005		0.005
	175.50	177.00	D001530	1.50	<0.005		0.001
	177.00	178.50	D001531	1.50	0.005		0.005
	178.50	180.00	D001532	1.50	0.005		0.005
	180.00	181.50	D001533	1.50	0.006		0.006
	181.50	183.00	D001534	1.50	<0.005		0.001
	183.00	184.50	D001535	1.50	<0.005		0.001
	184.50	186.00	D001537	1.50	<0.005		0.001
	186.00	187.50	D001538	1.50	<0.005		0.001
	187.50	189.00	D001539	1.50	<0.005		0.001
	189.00	190.50	D001540	1.50	<0.005		0.001
	190.50	192.00	D001541	1.50	0.006		0.006
	192.00	193.50	D001542	1.50	0.053		0.053
	193.50	195.00	D001543	1.50	0.007		0.007
	195.00	196.50	D001544	1.50	<0.005		0.001
	196.50	198.00	D001545	1.50	<0.005		0.001
	198.00	199.50	D001547	1.50	<0.005		0.001
	199.50	201.00	D001548	1.50	<0.005		0.001
	201.00	202.50	D001549	1.50	<0.005		0.001
	202.50	204.00	D001550	1.50	<0.005		0.001
	204.00	205.50	D001551	1.50	<0.005		0.001
	205.50	207.20	D001552	1.70	0.031		0.031
	207.20	208.50	D001553	1.30	0.242		0.242
	208.50	210.00	D001554	1.50	0.018		0.018
210.00	213.20	SY; POR	D001555	1.50	0.013		0.013
		<b>Syénite; Porphyrique</b>	D001557	1.70	<0.005		0.001
		syénite porphyrique à phénocristaux de FP 0.2-2 cm orienté	D001558	1.30	<0.005		0.001
		40-50° ac ( texture pseudo trachytique), forte hématisation ,	D001559	1.50	<0.005		0.001
		veines de QZ carbonaté, cheveux et veinules carbonatés,	D001560	1.50	0.019		0.019
		contacts 50-70° ac	D001561	1.50	<0.005		0.001
			D001562	1.50	0.010		0.010
			D001563	1.50	<0.005		0.001
			D001564	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	223.50	225.00	D001565	1.50	<0.005		0.001
	225.00	226.50	D001567	1.50	0.008		0.008
	226.50	228.00	D001568	1.50	<0.005		0.001
	228.00	229.50	D001569	1.50	0.005		0.005
	229.50	231.00	D001570	1.50	0.007		0.007
	231.00	232.50	D001571	1.50	0.010		0.010
	232.50	234.00	D001572	1.50	0.010		0.010
	234.00	235.50	D001573	1.50	0.007		0.007
	235.50	237.00	D001574	1.50	0.008		0.008
	237.00	238.50	D001575	1.50	0.014		0.014
	238.50	240.00	D001577	1.50	0.008		0.008
	240.00	241.50	D001578	1.50	0.015		0.015
	241.50	243.00	D001579	1.50	<0.005		0.001
	243.00	244.00	D001580	1.00	<0.005		0.001
	244.00	245.00	D001581	1.00	<0.005		0.001
	245.00	246.00	D001582	1.00	0.005		0.005
	246.00	247.00	D001583	1.00	0.006		0.006
	247.00	248.50	D001584	1.50	<0.005		0.001
	248.50	250.00	D001585	1.50	<0.005		0.001
	250.00	251.50	D001587	1.50	<0.005		0.001
	251.50	253.00	D001588	1.50	<0.005		0.001
	253.00	254.50	D001589	1.50	<0.005		0.001
	254.50	256.00	D001590	1.50	<0.005		0.001
	256.00	257.50	D001591	1.50	<0.005		0.001
	257.50	259.00	D001592	1.50	<0.005		0.001
	259.00	260.30	D001593	1.30	<0.005		0.001
	260.30	261.40	D001594	1.10	0.008		0.008
	261.40	263.00	D001595	1.60	<0.005		0.001
	263.00	264.50	D001597	1.50	0.010		0.010
	264.50	266.00	D001598	1.50	0.023		0.023
	266.00	267.00	D001599	1.00	<0.005		0.001
	267.00	268.10	D001600	1.10	<0.005		0.001
	268.10	269.50	D001601	1.40	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
276.00	282.00	CIS Cisaillement 30°	269.50	271.00	D001602	1.50	0.008		0.008
			271.00	272.50	D001603	1.50	0.035		0.035
			272.50	274.00	D001604	1.50	0.005		0.005
			274.00	275.50	D001605	1.50	<0.005		0.001
			275.50	277.00	D001607	1.50	<0.005		0.001
			277.00	278.50	D001608	1.50	<0.005		0.001
			278.50	280.00	D001609	1.50	<0.005		0.001
			280.00	281.50	D001610	1.50	0.007		0.007
			281.50	282.50	D001611	1.00	0.013		0.013
			282.50	284.00	D001612	1.50	<0.005		0.001
			284.00	285.50	D001613	1.50	0.008		0.008
			285.50	287.00	D001614	1.50	0.041		0.041
			287.00	288.50	D001615	1.50	<0.005		0.001
			288.50	290.00	D001617	1.50	0.019		0.019
			290.00	291.50	D001618	1.50	0.031		0.031
			291.50	293.00	D001619	1.50	0.008		0.008
			293.00	294.50	D001620	1.50	<0.005		0.001
			294.50	296.00	D001621	1.50	<0.005		0.001
			296.00	297.20	D001622	1.20	0.026		0.026
			297.20	298.50	D001623	1.30	0.045		0.045
298.50	300.00	D001624	1.50	0.013		0.013			
300.00	301.50	D001625	1.50	0.036		0.036			
301.50	303.00	D001627	1.50	0.020		0.020			
303.00	304.00	D001628	1.00	<0.005		0.001			
304.00	305.50	D001629	1.50	<0.005		0.001			
305.50	307.00	D001630	1.50	0.015		0.015			
307.00	308.50	D001631	1.50	<0.005		0.001			
308.50	310.00	D001632	1.50	0.005		0.005			
310.00	311.00	CIS Cisaillement 40°	310.00	311.50	D001633	1.50	0.033		0.033
			311.50	313.00	D001634	1.50	0.007		0.007
			313.00	314.50	D001635	1.50	0.040		0.040
			314.50	316.00	D001637	1.50	0.033		0.033
			316.00	317.00	D001638	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			317.00	318.00	D001639	1.00	1.090		1.090
317.50	318.00	FAI; CIS <b>Faille 30°; Cisaillement</b> faille ± 317.60 30° ac boue de faille verdâtre							
318.00	329.30	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique gris pâle, bréchique à sub bréchique, phénocristaux automorphe 0.2-0.7 cm irrég diss, silicification, localement séricitisé, veines et veinules de QZ carbonâtés, PY très fine irrég diss	318.00	319.50	D001640	1.50	2.320	5.08	2.320
			319.50	321.00	D001641	1.50	1.940		1.940
			321.00	322.50	D001642	1.50	1.450		1.450
			322.50	324.00	D001643	1.50	1.645		1.645
			324.00	325.50	D001644	1.50	4.790		5.080
			325.50	327.00	D001645	1.50	1.880		1.880
			327.00	328.30	D001647	1.30	1.265		1.265
			328.30	329.30	D001648	1.00	2.790		2.790
			329.30	330.50	D001649	1.20	1.155		1.155
			330.50	332.00	D001650	1.50	0.073		0.073
			332.00	333.50	D001651	1.50	0.253		0.253
			333.50	334.70	D001652	1.20	0.022		0.022
			334.70	335.80	D001653	1.10	0.129	0.129	
335.80	337.50	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique a texture sub trachytique, phénocristaux de FP sub allongés ou arrondis maclés, hématisation , localement sub bréchique, SR+, PY fine	335.80	337.50	D001654	1.70	0.165		0.165
337.50	341.50	SY; BRC <b>Syénite; Brèche de coulée</b> bréchique à sub bréchique, altération en calcite et silice, relique de phénocristaux localement orienté, cheveux en reseaux, SR++, BO+, PY fine diss, contact 60-70° ac	337.50	339.00	D001655	1.50	0.332		0.332
			339.00	340.50	D001657	1.50	0.664		0.664
			340.50	341.50	D001658	1.00	0.217		0.217
341.50	343.10	SY; FIN; RUB <b>Syénite; Grains fins; Rubané</b> syénite cisailé, altération en séricite, passage silicifié, veines de QZ carbonaté, veinules et cheveux localement // cisaillement, CL++, PY fine diss							
341.50	343.10	CIS <b>Cisaillement 40°</b>	341.50	343.10	D001659	1.60	0.742		0.742
343.10	344.30	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi, altération pervasive	343.10	344.30	D001660	1.20	0.799		0.799
			344.30	345.50	D001661	1.20	0.155		0.155

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		en silice, cheveux demembré, veinules 60-80° ac, SR+, PY fine	345.50	347.00	D001662	1.50	0.275		0.275
		diss	347.00	348.50	D001663	1.50	0.946		0.946
			348.50	350.00	D001664	1.50	0.644		0.644
			350.00	351.50	D001665	1.50	0.236		0.236
			351.50	353.00	D001667	1.50	0.268		0.268
			353.00	354.30	D001668	1.30	0.296		0.296
			354.30	355.50	D001669	1.20	1.185		1.185
			355.50	357.00	D001670	1.50	0.394		0.394
			357.00	358.50	D001671	1.50	0.334		0.334
			358.50	360.00	D001672	1.50	0.781		0.781
360.00	361.70	CIS	360.00	361.70	D001673	1.70	0.703		0.703
		<b>Cisaillement 40°</b>	361.70	363.00	D001674	1.30	0.479		0.479
			363.00	364.50	D001675	1.50	0.813		0.813
			364.50	366.00	D001677	1.50	1.240		1.240
			366.00	367.00	D001678	1.00	1.215		1.215
			367.00	368.00	D001679	1.00	1.040		1.040
368.00	372.90	SY; POR	368.00	369.50	D001680	1.50	0.861		0.861
		<b>Syénite; Porphyrique</b>	369.50	371.00	D001681	1.50	2.870		2.870
		altération en calcite, qlq phénocristaux mm, altération en silice,	371.00	372.00	D001682	1.00	2.380		2.380
		passage altéré en boïtite, PY fine diss	372.00	372.90	D001683	0.90	3.860	3.98	3.980
			372.90	373.90	D001684	1.00	1.705		1.705
373.90	375.20	FIN	373.90	375.20	D001685	1.30	3.350	3.29	3.290
		<b>Grains fins</b>							
		altération pervasive en silice, sub brêchification en debut d'éch,							
		qlq phénocristaux de FP mm							
375.20	384.10	TU; LAM; RUB; MAG	375.20	376.50	D001687	1.30	0.158		0.158
		<b>Tuf à cendre/lapillis; Laminations parallèles; Rubané;</b>	376.50	378.00	D001688	1.50	0.315		0.315
		<b>Magnétique</b>	378.00	379.50	D001689	1.50	<0.005		0.001
		tuf séricitisé et chloritisé, lits fin, localement plissées, passage avec	379.50	381.00	D001690	1.50	<0.005		0.001
		fragments carbonaté, légèrement cisailé, contact 20-30° ac	381.00	382.50	D001691	1.50	<0.005		0.001
			382.50	384.10	D001692	1.60	<0.005		0.001
384.10	387.00	BA; AMY; COU	384.10	385.40	D001693	1.30	<0.005		0.001
		<b>Basalte andésitique 30°; Amygdalaire; Coussiné</b>							
		basalte andésitique légèrement cisailé 30-40° ac, amygdules mm de							



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
385.40	387.00	CIS QZ et carbonâtes, alternance de niveaux à chlorite et séricite, veines de carbonâtes, veinules de carbonâtes et QZ	385.40	387.00	D001694	1.60	<0.005	0.001
		<b>Cisaillement 40°</b>						
387.00	388.50	TU; RUB; LAM Tuf à cendre/lapillis; Rubané; Laminations parallèles	387.00	388.50	D001695	1.50	<0.005	0.001
		tuf séricitisé et chloritisé, alternant de lits fin 30-50° ac à chlorite ou séricite, veinules et cheveux // litage 30-40° ac, veines de carbonâtes						
388.50	423.70	BA; MAS; MAG; AMY; COU Basalte andésitique; Roche massive; Magnétique; Amygdalaire; Coussiné	388.50	390.00	D001697	1.50	<0.005	0.001
		localement cisailé ou coussiné avec amygdules de QZ et carbonâtes, alternance de lits chloritisé et séricitisé., cheveux // cisaillement 30-40° ac, veines et veinules de carbonâtes, PY irrég diss	390.00	391.50	D001698	1.50	<0.005	0.001
			391.50	393.00	D001699	1.50	<0.005	0.001
			393.00	394.50	D001700	1.50	<0.005	0.001
			394.50	396.00	D001701	1.50	<0.005	0.001
			396.00	397.50	D001702	1.50	<0.005	0.001
			397.50	399.00	D001703	1.50	<0.005	0.001
			399.00	400.50	D001704	1.50	<0.005	0.001
			400.50	402.00	D001705	1.50	<0.005	0.001
			402.00	403.50	D001707	1.50	<0.005	0.001
			403.50	405.00	D001708	1.50	<0.005	0.001
			405.00	406.50	D001709	1.50	<0.005	0.001
			406.50	408.00	D001710	1.50	<0.005	0.001
			408.00	409.50	D001711	1.50	<0.005	0.001
			409.50	411.00	D001712	1.50	<0.005	0.001
			411.00	412.50	D001713	1.50	<0.005	0.001
			412.50	414.00	D001714	1.50	<0.005	0.001
			414.00	415.50	D001715	1.50	<0.005	0.001
			415.50	417.00	D001717	1.50	<0.005	0.001
			417.00	418.50	D001718	1.50	<0.005	0.001
			418.50	420.00	D001719	1.50	0.006	0.006
			420.00	421.50	D001720	1.50	<0.005	0.001
			421.50	422.60	D001721	1.10	<0.005	0.001
			422.60	423.70	D001722	1.10	<0.005	0.001
388.50	399.00	CIS Cisaillement 40° cisaillements 30-50° ac						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
423.70	437.20	TU; LAM <b>Tuf à cendre/lapillis; Laminations parallèles</b> litage 30-40° ac, alternance de lits fin à très fin, passage de graphite, cm, localement folié, PY fine et massive irrég diss	423.70	425.00	D001723	1.30	<0.005		0.001
			425.00	426.50	D001724	1.50	<0.005		0.001
			426.50	428.00	D001725	1.50	<0.005		0.001
			428.00	429.50	D001727	1.50	<0.005		0.001
			429.50	431.00	D001728	1.50	<0.005		0.001
			431.00	432.50	D001729	1.50	<0.005		0.001
			432.50	434.00	D001730	1.50	<0.005		0.001
			434.00	435.50	D001731	1.50	<0.005		0.001
			435.50	437.20	D001732	1.70	<0.005		0.001
437.20	Fin du sondage Nombre d'échantillons : 303 Nombre d'échantillons QAQC : 33 Longueur totale échantillonnée : 434.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	16.00	D001406	D001405	1.50	<0.005	0.001
28.00	29.50	D001416	A3	1.50	0.589	0.589
41.50	43.00	D001426	D001425	1.50	<0.005	0.001
54.00	55.50	D001436	M1	1.50	<0.005	0.001
66.50	68.00	D001446	D001445	1.50	<0.005	0.001
80.00	81.50	D001456	B4	1.50	2.610	2.610
93.50	95.00	D001466	D001465	1.50	0.030	0.030
106.00	107.50	D001476	M1	1.50	<0.005	0.001
118.50	120.00	D001486	D001485	1.50	0.210	0.210
131.00	132.50	D001496	C4	1.50	1.350	1.350
143.70	145.30	D001506	D001505	1.60	0.033	0.033
157.00	158.50	D001516	M1	1.50	<0.005	0.001
169.50	171.00	D001526	D001525	1.50	0.009	0.009
183.00	184.50	D001536	D2	1.50	0.853	0.853
196.50	198.00	D001546	D001545	1.50	<0.005	0.001
210.00	211.50	D001556	M1	1.50	<0.005	0.001
223.50	225.00	D001566	D001565	1.50	<0.005	0.001
237.00	238.50	D001576	F2	1.50	8.020	8.470
248.50	250.00	D001586	D001585	1.50	0.005	0.005
261.40	263.00	D001596	M1	1.60	<0.005	0.001
274.00	275.50	D001606	D001605	1.50	<0.005	0.001
287.00	288.50	D001616	G2	1.50	4.080	4.080
300.00	301.50	D001626	D001625	1.50	0.054	0.054
313.00	314.50	D001636	M1	1.50	<0.005	0.001
325.50	327.00	D001646	D001645	1.50	1.975	1.975
337.50	339.00	D001656	H	1.50	1.010	1.010
350.00	351.50	D001666	D001665	1.50	0.251	0.251
363.00	364.50	D001676	M1	1.50	<0.005	0.001
373.90	375.20	D001686	D001685	1.30	3.370	3.060
387.00	388.50	D001696	A3	1.50	0.602	0.602
400.50	402.00	D001706	D001705	1.50	<0.005	0.001
414.00	415.50	D001716	M1	1.50	<0.005	0.001
426.50	428.00	D001726	D001725	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-139</b>	Titre minier :	Section :
	Canton :	Niveau :
	Rang :	Place de travail :
Foré par : <b>Bradlay</b>	Lot :	
Décrit par : <b>Keith&amp; Hillar</b>	Du : 2010-03-11	Date de description :
	Au : 2010-03-13	

Collet

Azimut : 350.00°		UTM
Plongée : -60.00°	Est	630 510.0
Longueur : 93.21 m	Nord	5 374 549.8
	Élévation	293.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	349.50°	-60.40°	Oui	Reflex	38.00	349.90°	-59.80°	Oui
Reflex	5.00	348.60°	-59.70°	Non	Reflex	41.00	352.50°	-60.00°	Non
Reflex	8.00	346.40°	-59.60°	Oui	Reflex	44.00	350.60°	-59.80°	Non
Reflex	11.00	353.00°	-59.50°	Oui	Reflex	47.00	351.80°	-60.20°	Non
Reflex	14.00	347.50°	-59.80°	Non	Reflex	50.00	349.00°	-59.90°	Oui
Reflex	17.00	350.00°	-59.80°	Non	Reflex	53.00	351.90°	-59.80°	Non
Reflex	20.00	353.10°	-59.80°	Non	Reflex	56.00	350.60°	-60.10°	Non
Reflex	23.00	351.00°	-59.60°	Non	Reflex	59.00	352.30°	-60.00°	Non
Reflex	26.00	351.60°	-60.10°	Non	Reflex	62.00	352.10°	-60.10°	Non
Reflex	29.00	352.10°	-59.80°	Non	Reflex	65.00	352.40°	-60.10°	Non
Reflex	32.00	352.00°	-59.80°	Non	Reflex	68.00	349.10°	-59.80°	Non
Reflex	35.00	351.30°	-59.90°	Non	Reflex	71.00	350.20°	-59.90°	Non

Description

Dimension de la carotte :	Cimenté : Non	Entreposé : Non
---------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	351.50°	-59.70°	Non					
Reflex	77.00	350.80°	-59.90°	Non					
Reflex	80.00	351.80°	-59.90°	Non					
Reflex	83.00	350.20°	-59.60°	Non					
Reflex	86.00	350.70°	-59.20°	Non					
Reflex	89.00	352.60°	-59.70°	Oui					
Reflex	92.00	350.80°	-59.40°	Non					
Reflex	93.20	350.80°	-59.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT Mort-terrain Mort-terrain						
2.20	93.20	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique, localement carbonatée, et parfois séricitisée.	2.20	3.50	D010821	1.30	<0.005	0.001
			3.50	5.00	D010822	1.50	<0.005	0.001
			5.00	6.50	D010823	1.50	<0.005	0.001
			6.50	8.00	D010824	1.50	0.005	0.005
			8.00	9.50	D010826	1.50	0.006	0.006
			9.50	11.00	D010827	1.50	<0.005	0.001
			11.00	12.50	D010828	1.50	0.006	0.006
			12.50	14.00	D010829	1.50	<0.005	0.001
			14.00	15.50	D010830	1.50	<0.005	0.001
			15.50	17.00	D010831	1.50	<0.005	0.001
			17.00	18.50	D010832	1.50	<0.005	0.001
			18.50	20.00	D010833	1.50	<0.005	0.001
			20.00	21.50	D010834	1.50	<0.005	0.001
			21.50	23.00	D010836	1.50	<0.005	0.001
			23.00	24.50	D010837	1.50	<0.005	0.001
			24.50	26.00	D010838	1.50	0.006	0.006
			26.00	27.50	D010839	1.50	0.007	0.007
			27.50	29.00	D010840	1.50	0.009	0.009
			29.00	30.30	D010841	1.30	0.081	0.081
			30.30	31.20	D010842	0.90	0.256	0.256
			31.20	32.90	D010843	1.70	<0.005	0.001
			32.90	34.50	D010844	1.60	0.008	0.008
			34.50	36.00	D010846	1.50	<0.005	0.001
			36.00	37.50	D010847	1.50	<0.005	0.001
			37.50	39.00	D010848	1.50	<0.005	0.001
			39.00	40.50	D010849	1.50	<0.005	0.001
			40.50	42.00	D010850	1.50	<0.005	0.001
			42.00	43.50	D010851	1.50	0.014	0.014
			43.50	44.40	D010852	0.90	0.008	0.008
			45.70	47.00	D010853	1.30	0.006	0.006
			47.00	48.50	D010854	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
2.20	66.50	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique carbonatée avec passages de sections oxydées jusqu'à 17.0 cm, localement séricitiséeveinules et injections de cb-cc parfois démembrées, py fine et automorphe irrér diss.	48.50	50.00	D010856	1.50	<0.005		0.001
			50.00	51.50	D010857	1.50	0.010		0.010
			51.50	53.00	D010858	1.50	<0.005		0.001
			53.00	54.50	D010859	1.50	0.062		0.062
			54.50	56.00	D010860	1.50	0.056		0.056
			56.00	57.50	D010861	1.50	0.007		0.007
			57.50	59.00	D010862	1.50	0.008		0.008
			59.00	60.40	D010863	1.40	0.009		0.009
			60.40	62.00	D010864	1.60	0.011		0.011
			62.00	63.50	D010866	1.50	<0.005		0.001
66.50	93.20	SY; MAS <b>Syénite; Roche massive</b> Massive et carbonatée, parfois très carbonatée, localement reliques de phénocristaux, l'intensité de la séricitisation augmente avec la profondeur, parfois silicifié et sub-bréchiq, py fine, en amas et automorphe irrég diss.	63.50	65.00	D010867	1.50	0.007		0.007
			65.00	66.50	D010868	1.50	0.018		0.018
			66.50	68.00	D010869	1.50	0.014		0.014
			68.00	69.50	D010870	1.50	<0.005		0.001
			69.50	71.00	D010871	1.50	0.008		0.008
			71.00	72.50	D010872	1.50	<0.005		0.001
			72.50	74.00	D010873	1.50	<0.005		0.001
			74.00	75.50	D010874	1.50	0.019		0.019
			75.50	77.00	D010876	1.50	0.045		0.045
			77.00	78.00	D010877	1.00	0.373		0.373
			78.00	79.50	D010878	1.50	4.650	4.42	4.420
			79.50	81.00	D010879	1.50	5.670	5.51	5.510
			81.00	82.50	D010880	1.50	>10.0	10.65	10.650
			82.50	84.00	D010881	1.50	>10.0	10.70	10.700
			84.00	85.50	D010882	1.50	>10.0	20.90	20.900
			85.50	87.00	D010883	1.50	5.930	6.08	6.080
			87.00	88.50	D010884	1.50	1.170		1.170
			88.50	90.00	D010886	1.50	3.300	3.50	3.500

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
93.20	93.21	OM Ouverture minière	90.00	91.00	D010887	1.00	2.680	15.20	2.680
			91.00	92.00	D010888	1.00	1.640		1.640
			92.00	93.20	D010889	1.20	>10.0		15.200
93.21	Fin du sondage Nombre d'échantillons : 62 Nombre d'échantillons QAQC : 7 Longueur totale échantillonnée : 89.70								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.50	8.00	D010825	D2	1.50	0.851	0.851
20.00	21.50	D010835	D010834	1.50	<0.005	0.001
32.90	32.90	D010845	M1	0.00	<0.005	0.001
47.00	48.50	D010855	D010854	1.50	0.005	0.005
60.40	60.40	D010865	F2	0.00	8.220	7.990
74.00	75.50	D010875	D010874	1.50	0.016	0.016
87.00	87.00	D010885	M1	0.00	0.017	0.017

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-140**

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail :

Foré par :      Bradley

Lot :

Décrit par :      David Ruhara

Du :                      2010-03-13

Date de description :

Au :                      2010-03-14

Collet

Azimut :              344.00°  
 Plongée :             -54.00°  
 Longueur :          122.00 m

UTM

Est	630 515.0
Nord	5 374 585.6
Élévation	286.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	345.30°	-54.50°	Non
Reflex	5.00	345.60°	-54.40°	Non
Reflex	8.00	345.40°	-54.40°	Non
Reflex	11.00	345.10°	-54.30°	Non
Reflex	14.00	344.90°	-54.60°	Non
Reflex	17.00	345.50°	-54.40°	Non
Reflex	20.00	345.40°	-54.40°	Non
Reflex	23.00	345.40°	-54.40°	Non
Reflex	26.00	345.30°	-54.40°	Non
Reflex	29.00	345.20°	-54.40°	Non
Reflex	32.00	345.20°	-54.40°	Non
Reflex	35.00	345.10°	-54.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	345.00°	-54.30°	Non
Reflex	41.00	345.00°	-54.20°	Non
Reflex	44.00	344.90°	-54.10°	Non
Reflex	47.00	344.80°	-54.10°	Non
Reflex	50.00	344.70°	-54.10°	Non
Reflex	53.00	344.60°	-54.00°	Non
Reflex	56.00	344.40°	-53.90°	Non
Reflex	59.00	344.20°	-53.90°	Non
Reflex	62.00	344.00°	-53.80°	Non
Reflex	65.00	343.80°	-53.80°	Non
Reflex	68.00	343.60°	-53.70°	Non
Reflex	71.00	343.70°	-53.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	343.70°	-53.70°	Non					
Reflex	77.00	343.70°	-53.70°	Non					
Reflex	80.00	343.90°	-53.70°	Non					
Reflex	83.00	343.80°	-53.70°	Non					
Reflex	86.00	344.40°	-53.70°	Non					
Reflex	89.00	343.90°	-53.60°	Non					
Reflex	92.00	344.10°	-53.60°	Non					
Reflex	95.00	345.00°	-53.70°	Non					
Reflex	98.00	345.30°	-53.50°	Non					
Reflex	101.00	344.40°	-53.60°	Non					
Reflex	104.00	345.10°	-53.50°	Non					
Reflex	107.00	345.30°	-53.50°	Non					
Reflex	110.00	344.20°	-53.20°	Non					
Reflex	113.00	344.00°	-53.30°	Non					
Reflex	116.00	343.70°	-53.20°	Non					
Reflex	119.00	345.40°	-53.40°	Non					
Reflex	122.00	344.80°	-53.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT						
		<b>Mort-terrain</b>						
3.00	18.00	SY; POR	3.00	4.50	D005388	1.50	0.025	0.025
		<b>Syénite; Porphyrique</b>	4.50	6.00	D005389	1.50	0.037	0.037
		Syénite porphyrique à tendance équi-granulaire, phénocristaux Xmm , diminuant vers le contact infér, ++ magnétisé, rouge et peu verdâtre.	6.00	7.50	D005390	1.50	0.334	0.334
			7.50	9.00	D005391	1.50	0.094	0.094
			9.00	10.50	D005392	1.50	0.076	0.076
			10.50	12.00	D005393	1.50	0.168	0.168
			12.00	13.50	D005394	1.50	0.207	0.207
			13.50	15.00	D005395	1.50	0.253	0.253
			15.00	16.50	D005396	1.50	0.420	0.420
			16.50	18.00	D005398	1.50	0.495	0.495
18.00	96.50	BA; MAS; FIN; AMY; COU	18.00	19.00	D005399	1.00	0.777	0.777
		<b>Basalte andésitique; Roche massive; Grains fins;</b>	19.00	20.50	D005400	1.50	0.140	0.140
		<b>Amygdalaire; Coussiné</b>	20.50	22.00	D005401	1.50	0.005	0.005
		Basalte andésitique à texture amygdalaire , massive , grains fins et de passage coussiné.	22.00	23.50	D005402	1.50	0.006	0.006
			23.50	25.00	D005403	1.50	0.006	0.006
			25.00	26.50	D005404	1.50	<0.005	0.001
			26.50	28.00	D005405	1.50	0.006	0.006
			28.00	29.50	D005406	1.50	<0.005	0.001
			29.50	31.00	D005408	1.50	<0.005	0.001
			31.00	32.50	D005409	1.50	<0.005	0.001
			32.50	34.00	D005410	1.50	<0.005	0.001
			34.00	35.50	D005411	1.50	<0.005	0.001
			35.50	37.00	D005412	1.50	0.006	0.006
			37.00	38.50	D005413	1.50	<0.005	0.001
			38.50	40.00	D005414	1.50	<0.005	0.001
			40.00	41.50	D005415	1.50	<0.005	0.001
			41.50	43.00	D005416	1.50	<0.005	0.001
			43.00	44.50	D005418	1.50	<0.005	0.001
			44.50	46.00	D005419	1.50	<0.005	0.001
			46.00	47.50	D005420	1.50	<0.005	0.001
			47.50	49.00	D005421	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.00	50.50	D005423	1.50	<0.005		0.001
	50.50	52.00	D005424	1.50	<0.005		0.001
	52.00	53.50	D005425	1.50	<0.005		0.001
	53.50	55.00	D005426	1.50	<0.005		0.001
	55.00	56.50	D005428	1.50	<0.005		0.001
	56.50	58.00	D005429	1.50	<0.005		0.001
	58.00	59.50	D005430	1.50	<0.005		0.001
	59.50	61.00	D005431	1.50	<0.005		0.001
	61.00	62.50	D005432	1.50	<0.005		0.001
	62.50	64.00	D005433	1.50	<0.005		0.001
	64.00	65.50	D005434	1.50	<0.005		0.001
	65.50	67.00	D005435	1.50	<0.005		0.001
	67.00	68.50	D005436	1.50	<0.005		0.001
	68.50	70.00	D005438	1.50	0.005		0.005
	70.00	71.50	D005439	1.50	<0.005		0.001
	71.50	73.00	D005440	1.50	0.005		0.005
	73.00	74.50	D005441	1.50	0.005		0.005
	74.50	76.00	D005442	1.50	0.005		0.005
	76.00	77.50	D005443	1.50	<0.005		0.001
	77.50	79.00	D005444	1.50	<0.005		0.001
	79.00	80.50	D005445	1.50	<0.005		0.001
	80.50	82.00	D005446	1.50	<0.005		0.001
	82.00	83.50	D005448	1.50	0.005		0.005
	83.50	85.00	D005449	1.50	<0.005		0.001
	85.00	86.50	D005450	1.50	0.005		0.005
	86.50	88.00	D005451	1.50	<0.005		0.001
	88.00	89.50	D005452	1.50	<0.005		0.001
	89.50	91.00	D005453	1.50	<0.005		0.001
	91.00	92.50	D005454	1.50	<0.005		0.001
	92.50	94.00	D005455	1.50	<0.005		0.001
	94.00	95.00	D005456	1.00	<0.005		0.001
	95.00	96.50	D005458	1.50	<0.005		0.001
96.50	122.00		D005459	1.50	0.006		0.006

GR; FIN; MTY; GRO

Grès; Grains fins; Grains moyens; Grains grossiers

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Sédiment clastique, grès à grains fins à grossiers et qlq passage à fragments. Passage volcano-pyroclastique avec couche graphiteuse, qlq choses d'allure de fantômes des amugdules, qlq veines de CB.	98.00	99.50	D005460	1.50	<0.005		0.001
	99.50	101.00	D005461	1.50	0.005		0.005
	101.00	102.50	D005463	1.50	<0.005		0.001
	102.50	104.00	D005464	1.50	<0.005		0.001
	104.00	105.50	D005465	1.50	0.006		0.006
	105.50	107.00	D005466	1.50	0.005		0.005
	107.00	108.50	D005468	1.50	0.005		0.005
	108.50	110.00	D005469	1.50	0.005		0.005
	110.00	111.50	D005470	1.50	0.005		0.005
	111.50	113.00	D005471	1.50	<0.005		0.001
	113.00	114.50	D005472	1.50	<0.005		0.001
	114.50	116.00	D005473	1.50	<0.005		0.001
	116.00	117.50	D005474	1.50	<0.005		0.001
	117.50	119.00	D005475	1.50	<0.005		0.001
	119.00	120.50	D005476	1.50	0.006		0.006
	120.50	122.00	D005478	1.50	0.005		0.005
	122.00	Fin du sondage Nombre d'échantillons : 80 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 119.00					

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
3.00	4.50	D005387	F2	1.50	8.530	8.450
15.00	16.50	D005397	D005396	1.50	0.445	0.445
28.00	29.50	D005407	H2	1.50	0.989	0.989
41.50	43.00	D005417	D005416	1.50	<0.005	0.001
47.50	49.00	D005422	M1	1.50	<0.005	0.001
53.50	55.00	D005427	D2	1.50	0.816	0.816
67.00	68.50	D005437	D005436	1.50	<0.005	0.001
80.50	82.00	D005447	A3	1.50	0.591	0.591
94.00	95.00	D005457	D005456	1.00	<0.005	0.001
99.50	101.00	D005462	M1	1.50	<0.005	0.001
105.50	107.00	D005467	G2	1.50	4.070	4.070
119.00	120.50	D005477	D005476	1.50	0.006	0.006

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-141**

Titre minier :

Section :                      630 600

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :            Guy Gbaguidi

Du :                      2010-03-14

Date de description :    2010-03-20

Au :                      2010-03-15

Collet

UTM

Azimut :                0.00°  
 Plongée :               -55.00°  
 Longueur :            125.21 m

Est	630 600.3
Nord	5 374 590.5
Élévation	286.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	155.20°	-53.90°	Oui
Reflex	5.00	359.70°	-54.50°	Non
Reflex	8.00	358.90°	-54.60°	Non
Reflex	11.00	359.30°	-54.40°	Non
Reflex	14.00	1.00°	-54.20°	Non
Reflex	17.00	357.80°	-53.90°	Non
Reflex	20.00	358.60°	-54.00°	Non
Reflex	23.00	358.70°	-53.90°	Non
Reflex	26.00	359.00°	-53.90°	Non
Reflex	29.00	359.90°	-53.90°	Non
Reflex	32.00	359.50°	-53.80°	Non
Reflex	35.00	359.00°	-53.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.00°	-53.40°	Non
Reflex	41.00	359.20°	-53.20°	Non
Reflex	44.00	358.30°	-53.00°	Oui
Reflex	47.00	359.20°	-53.10°	Non
Reflex	50.00	359.20°	-52.90°	Non
Reflex	53.00	359.70°	-52.90°	Non
Reflex	56.00	359.50°	-52.80°	Non
Reflex	59.00	359.10°	-52.60°	Non
Reflex	62.00	358.10°	-52.30°	Non
Reflex	65.00	357.60°	-52.10°	Oui
Reflex	68.00	358.90°	-52.20°	Non
Reflex	71.00	358.10°	-51.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	358.60°	-51.70°	Non					
Reflex	77.00	358.60°	-51.70°	Non					
Reflex	80.00	358.40°	-51.60°	Non					
Reflex	83.00	355.80°	-49.50°	Non					
Reflex	86.00	357.30°	-51.20°	Non					
Reflex	89.00	358.30°	-51.30°	Non					
Reflex	92.00	358.30°	-51.30°	Non					
Reflex	95.00	357.20°	-51.00°	Non					
Reflex	98.00	356.80°	-50.90°	Oui					
Reflex	101.00	357.90°	-50.90°	Non					
Reflex	104.00	357.20°	-50.70°	Non					
Reflex	107.00	357.00°	-50.50°	Non					
Reflex	110.00	358.10°	-50.80°	Non					
Reflex	113.00	357.30°	-50.40°	Non					
Reflex	116.00	357.70°	-50.30°	Non					
Reflex	119.00	358.00°	-50.10°	Non					
Reflex	122.00	357.60°	-49.70°	Non					
Reflex	125.00	357.80°	-49.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.80	MT						
		<b>Mort-terrain</b>						
5.80	31.70	SY	5.80	7.50	D010073	1.70	0.042	0.042
		<b>Syénite</b>						
		Syénite carbonaté, faiblement magnétique, rose à rose-verdâtre, passages de d'oxydes de carbonate, localement séricitisée et verdâtre.	7.50	9.00	D010074	1.50	0.020	0.020
			9.00	10.50	D010075	1.50	0.010	0.010
			10.50	12.00	D010076	1.50	0.014	0.014
			12.00	13.50	D010077	1.50	<0.005	0.001
			13.50	15.00	D010078	1.50	0.005	0.005
			15.00	16.50	D010079	1.50	<0.005	0.001
			16.50	18.00	D010080	1.50	<0.005	0.001
			18.00	19.50	D010081	1.50	<0.005	0.001
			19.50	21.00	D010082	1.50	<0.005	0.001
			21.00	22.00	D010084	1.00	0.034	0.034
			22.00	23.10	D010085	1.10	0.240	0.240
			23.10	24.20	D010086	1.10	<0.005	0.001
			24.20	25.50	D010087	1.30	0.108	0.108
			25.50	27.00	D010088	1.50	0.006	0.006
			27.00	28.50	D010089	1.50	0.025	0.025
			28.50	30.00	D010090	1.50	<0.005	0.001
			30.00	31.50	D010091	1.50	0.322	0.322
31.20	32.00	FAI	31.50	33.00	D010092	1.50	1.730	1.730
		<b>Faille 15°</b>						
		Présence de boue (gouge)						
31.70	57.30	BA	33.00	34.00	D010094	1.00	0.007	0.007
		<b>Basalte</b>						
		Basalte amygdulaire vert-claire, massive à gf, cisailé à 20' du CA, fortement carbonaté, py en traces.	34.00	35.50	D010095	1.50	<0.005	0.001
			35.50	37.00	D010096	1.50	<0.005	0.001
			37.00	38.50	D010097	1.50	<0.005	0.001
			38.50	40.00	D010098	1.50	<0.005	0.001
			40.00	41.00	D010099	1.00	<0.005	0.001
			41.00	42.50	D010100	1.50	<0.005	0.001
			42.50	44.00	D010101	1.50	<0.005	0.001
			44.00	45.50	D010102	1.50	<0.005	0.001
			45.50	47.00	D010104	1.50	<0.005	0.001
			47.00	48.50	D010105	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
57.30	82.80	TU <b>Tuf à cendre/lapillis</b> Tuf à cendre carbonaté avec localement horizons graphiteux, traces de py	48.50	50.00	D010106	1.50	<0.005		0.001
			50.00	51.50	D010107	1.50	<0.005		0.001
			51.50	53.00	D010108	1.50	<0.005		0.001
			53.00	54.50	D010109	1.50	<0.005		0.001
			54.50	56.00	D010110	1.50	<0.005		0.001
			56.00	57.30	D010111	1.30	<0.005		0.001
			57.30	59.00	D010112	1.70	<0.005		0.001
			59.00	60.00	D010114	1.00	<0.005		0.001
			60.00	61.50	D010115	1.50	<0.005		0.001
			61.50	63.00	D010116	1.50	<0.005		0.001
			63.00	64.50	D010117	1.50	<0.005		0.001
			64.50	66.00	D010118	1.50	<0.005		0.001
			66.00	67.50	D010119	1.50	<0.005		0.001
			67.50	69.00	D010120	1.50	<0.005		0.001
			69.00	70.50	D010121	1.50	<0.005		0.001
			70.50	72.00	D010122	1.50	<0.005		0.001
			72.00	73.70	D010124	1.70	0.005		0.005
			73.70	75.00	D010125	1.30	<0.005		0.001
			75.00	76.50	D010126	1.50	<0.005		0.001
			76.50	78.00	D010127	1.50	<0.005		0.001
78.00	79.50	D010128	1.50	<0.005		0.001			
79.50	81.10	D010129	1.60	<0.005		0.001			
81.10	82.80	D010130	1.70	<0.005		0.001			
82.80	97.20	BA <b>Basalte</b> Massive à gf, séricitisé fortement carbonaté, localement, passages de niveau graphiteux, py irrég diss.	82.80	84.50	D010131	1.70	<0.005		0.001
			84.50	86.00	D010132	1.50	<0.005		0.001
			86.00	87.50	D010134	1.50	<0.005		0.001
			87.50	89.00	D010135	1.50	<0.005		0.001
			89.00	90.50	D010136	1.50	0.005		0.005
			90.50	92.00	D010137	1.50	0.005		0.005
			92.00	93.50	D010138	1.50	<0.005		0.001
			93.50	95.00	D010139	1.50	<0.005		0.001
			95.00	96.00	D010140	1.00	<0.005		0.001
			96.00	97.20	D010141	1.20	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
97.20	98.80	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique gris-foncé.							
97.20	98.80	SY; POR <b>Syénite; Porphyrique</b> Syénite séricitisée avec localement, oxyde de carbonate.	97.20	98.80	D010142	1.60	0.006		0.006
98.80	101.20	BA <b>Basalte</b> Basalte vert-pâle	98.80	100.00	D010144	1.20	<0.005		0.001
			100.00	101.20	D010145	1.20	<0.005		0.001
101.20	109.40	PT <b>Porphyre trachytique</b> Porphyre trachytique vert-pâle, séricitisé, carbonaté.	101.20	102.50	D010146	1.30	<0.005		0.001
			102.50	104.00	D010147	1.50	0.008		0.008
			104.00	105.00	D010148	1.00	<0.005		0.001
			105.00	106.00	D010149	1.00	<0.005		0.001
			106.00	107.00	D010150	1.00	<0.005		0.001
			107.00	108.00	D010151	1.00	<0.005		0.001
			108.00	109.40	D010152	1.40	<0.005		0.001
109.40	125.20	BA <b>Basalte</b> Basalte, passage de niveau graphiteux, localement gloméroporphyrique, py irrég diss.	109.40	110.50	D010154	1.10	0.005		0.005
110.50	111.70	MS <b>Mudstone</b> Mudstone graphiteux avec 40.0 cm de bas au contact inf.	110.50	111.70	D010155	1.20	0.008		0.008
111.70	113.20	PG <b>Porphyre gloméroporphyrique</b> Gris-foncé avec teinte verdâtre, séricitisé, silicifié et carbonaté.	111.70	113.20	D010156	1.50	<0.005		0.001
			113.20	114.90	D010157	1.70	<0.005		0.001
			114.90	116.50	D010158	1.60	<0.005		0.001
			116.50	118.00	D010159	1.50	<0.005		0.001
			118.00	119.50	D010160	1.50	<0.005		0.001
			119.50	121.00	D010161	1.50	<0.005		0.001
			121.00	122.50	D010162	1.50	<0.005		0.001
			122.50	124.00	D010163	1.50	<0.005		0.001
			124.00	125.20	D010164	1.20	<0.005		0.001
125.20	125.21	OM <b>Ouverture minière</b> EOH							

125.21

Fin du sondage

Nombre d'échantillons : 84

Nombre d'échantillons QAQC : 8

Longueur totale échantillonnée : 119.40

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
19.50	21.00	D010083	D010082	1.50	<0.005	0.001
31.50	33.00	D010093	A3	1.50	0.613	0.613
44.00	45.50	D010103	D010102	1.50	<0.005	0.001
57.30	59.00	D010113	M1	1.70	<0.005	0.001
70.50	72.00	D010123	D010122	1.50	<0.005	0.001
84.50	86.00	D010133	B4	1.50	2.630	2.630
97.20	98.80	D010143	D010142	1.60	<0.005	0.001
108.00	109.40	D010153	C3	1.40	1.335	1.335

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-142**

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail :

Foré par :      Bradley

Lot :

Décrit par :      David Ruhara

Du :                      2010-03-15

Date de description :

Au :                      2010-03-17

Collet

UTM

Azimut :              0.00°  
 Plongée :             -60.00°  
 Longueur :          83.71 m

Est	630 000.1
Nord	5 374 350.8
Élévation	282.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	348.80°	-59.90°	Oui
Reflex	5.00	163.70°	-59.70°	Oui
Reflex	8.00	1.90°	-59.80°	Non
Reflex	11.00	3.10°	-59.90°	Non
Reflex	14.00	2.90°	-59.90°	Non
Reflex	17.00	1.60°	-59.90°	Non
Reflex	20.00	0.40°	-59.70°	Non
Reflex	23.00	0.70°	-59.70°	Non
Reflex	26.00	0.30°	-59.50°	Non
Reflex	29.00	2.60°	-59.60°	Non
Reflex	32.00	1.60°	-59.50°	Non
Reflex	35.00	1.10°	-59.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.30°	-59.50°	Non
Reflex	41.00	2.80°	-59.50°	Non
Reflex	44.00	360.00°	-59.60°	Non
Reflex	47.00	0.00°	-59.60°	Non
Reflex	50.00	2.60°	-59.50°	Non
Reflex	53.00	0.50°	-59.50°	Non
Reflex	56.00	0.90°	-59.40°	Non
Reflex	59.00	0.90°	-59.40°	Non
Reflex	62.00	359.30°	-59.40°	Non
Reflex	65.00	2.10°	-59.50°	Non
Reflex	68.00	2.10°	-59.40°	Non
Reflex	71.00	0.60°	-59.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.60°	-59.40°	Non					
Reflex	77.00	359.60°	-59.30°	Non					
Reflex	80.00	1.60°	-60.30°	Non					
Reflex	83.00	2.00°	-63.50°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	9.00	MT						
		<b>Mort-terrain</b>						
9.00	83.70	SY; POR	9.00	10.50	D005479	1.50	0.005	0.005
		<b>Syénite; Porphyrique</b>						
		Syénite porphyrique à phénocristaux Xmm à rarement Xcm, avec de passage sans ou peu de phénocristaux,rouge.						
			10.50	12.00	D005480	1.50	<0.005	0.001
			12.00	13.50	D005481	1.50	<0.005	0.001
			13.50	15.00	D005482	1.50	<0.005	0.001
			15.00	16.50	D005483	1.50	0.010	0.010
			16.50	18.00	D005484	1.50	<0.005	0.001
			18.00	19.50	D005485	1.50	<0.005	0.001
			19.50	21.00	D005486	1.50	0.082	0.082
			21.00	22.50	D005488	1.50	0.441	0.441
			22.50	24.00	D005489	1.50	0.062	0.062
			24.00	25.50	D005490	1.50	0.006	0.006
			25.50	27.00	D005491	1.50	0.010	0.010
			27.00	28.50	D005492	1.50	0.015	0.015
			28.50	30.00	D005493	1.50	<0.005	0.001
			30.00	31.50	D005494	1.50	0.027	0.027
			31.50	33.00	D005495	1.50	0.064	0.064
			33.00	34.50	D005496	1.50	0.125	0.125
			34.50	36.00	D005498	1.50	0.320	0.320
			36.00	37.50	D005499	1.50	0.138	0.138
			37.50	39.00	D005500	1.50	<0.005	0.001
			39.00	40.50	D006001	1.50	0.563	0.563
			40.50	42.00	D006003	1.50	0.231	0.231
			42.00	43.50	D006004	1.50	<0.005	0.001
			43.50	45.00	D006005	1.50	<0.005	0.001
			45.00	46.50	D006006	1.50	<0.005	0.001
			46.50	48.00	D006008	1.50	0.034	0.034
			48.00	49.50	D006009	1.50	0.021	0.021
			49.50	51.00	D006010	1.50	0.689	0.689
			51.00	52.50	D006011	1.50	0.362	0.362
			52.50	54.00	D006012	1.50	0.159	0.159
			54.00	55.50	D006013	1.50	0.087	0.087
			55.50	57.00	D006014	1.50	0.057	0.057

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
83.70	57.00	58.50	D006015	1.50	0.035	3.06	0.035
	58.50	60.00	D006016	1.50	0.010		0.010
	60.00	61.50	D006018	1.50	<0.005		0.001
	61.50	63.00	D006019	1.50	<0.005		0.001
	63.00	64.50	D006020	1.50	0.014		0.014
	64.50	66.00	D006021	1.50	0.013		0.013
	66.00	67.50	D006022	1.50	0.005		0.005
	67.50	69.00	D006023	1.50	<0.005		0.001
	69.00	70.50	D006024	1.50	0.218		0.218
	70.50	72.00	D006025	1.50	2.230		2.230
	72.00	73.50	D006026	1.50	0.081		0.081
	73.50	75.00	D006028	1.50	0.158		0.158
	75.00	76.50	D006029	1.50	0.324		0.324
	76.50	78.00	D006030	1.50	0.098		0.098
	78.00	79.50	D006031	1.50	0.012		0.012
	79.50	81.00	D006032	1.50	0.145		0.145
	81.00	82.00	D006033	1.00	0.237		0.237
	82.00	83.70	D006034	1.70	3.010		3.060
83.71	83.71	OM					
		Ouverture minière					
83.71	Fin du sondage						
	Nombre d'échantillons : 50						
	Nombre d'échantillons QAQC : 6						
	Longueur totale échantillonnée : 74.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
19.50	21.00	D005487	C4	1.50	1.320	1.320
33.00	34.50	D005497	D005496	1.50	0.151	0.151
39.00	40.50	D006002	M1	1.50	<0.005	0.001
45.00	46.50	D006007	A3	1.50	0.617	0.617
58.50	60.00	D006017	D006016	1.50	0.008	0.008
73.50	75.00	D006027	H2	1.50	0.983	0.983

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-143**

Titre minier :

Section :                      630 000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :

Lot :

Décrit par :

Du :                      2010-03-16

Date de description :

Au :                      2010-03-21

Collet

UTM

Azimut :                      180.00°

Plongée :                      -73.00°

Longueur :                      330.00 m

Est                      629 999.9

Nord                      5 374 350.7

Élévation                      282.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	351.60°	-72.90°	Oui
Reflex	5.00	351.60°	-73.00°	Oui
Reflex	8.00	351.60°	-72.90°	Oui
Reflex	11.00	183.40°	-73.20°	Non
Reflex	14.00	183.30°	-73.20°	Non
Reflex	17.00	183.00°	-73.30°	Non
Reflex	20.00	183.30°	-72.90°	Non
Reflex	23.00	183.30°	-73.00°	Non
Reflex	26.00	184.10°	-73.00°	Non
Reflex	29.00	183.40°	-73.00°	Non
Reflex	32.00	181.30°	-73.00°	Non
Reflex	35.00	182.60°	-73.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	182.10°	-73.00°	Non
Reflex	41.00	180.70°	-73.00°	Oui
Reflex	44.00	181.70°	-73.10°	Non
Reflex	47.00	182.50°	-73.10°	Non
Reflex	50.00	182.00°	-73.10°	Non
Reflex	53.00	183.20°	-73.10°	Non
Reflex	56.00	179.40°	-73.10°	Oui
Reflex	59.00	182.70°	-73.10°	Non
Reflex	62.00	182.50°	-73.00°	Non
Reflex	65.00	182.30°	-73.00°	Non
Reflex	68.00	182.50°	-73.00°	Non
Reflex	71.00	182.20°	-73.00°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	182.50°	-73.10°	Non	Reflex	173.00	188.40°	-70.20°	Non
Reflex	77.00	182.80°	-73.10°	Non	Reflex	176.00	188.40°	-70.10°	Non
Reflex	80.00	183.10°	-73.00°	Non	Reflex	179.00	188.50°	-69.90°	Non
Reflex	83.00	182.50°	-73.00°	Non	Reflex	182.00	188.20°	-69.80°	Non
Reflex	86.00	183.10°	-73.00°	Non	Reflex	185.00	188.00°	-69.60°	Non
Reflex	89.00	182.60°	-73.10°	Non	Reflex	188.00	188.00°	-69.50°	Non
Reflex	92.00	183.50°	-73.00°	Non	Reflex	191.00	188.10°	-69.50°	Non
Reflex	95.00	183.90°	-72.90°	Non	Reflex	194.00	187.80°	-69.30°	Non
Reflex	98.00	184.30°	-72.90°	Non	Reflex	197.00	187.70°	-69.10°	Non
Reflex	101.00	184.40°	-72.80°	Non	Reflex	200.00	187.60°	-69.10°	Non
Reflex	104.00	184.70°	-72.80°	Non	Reflex	203.00	187.80°	-68.70°	Non
Reflex	107.00	185.10°	-72.80°	Non	Reflex	206.00	188.10°	-68.50°	Non
Reflex	110.00	185.40°	-72.70°	Non	Reflex	209.00	188.40°	-68.30°	Non
Reflex	113.00	185.50°	-72.70°	Non	Reflex	212.00	188.60°	-68.10°	Non
Reflex	116.00	185.60°	-72.40°	Non	Reflex	215.00	188.40°	-67.80°	Non
Reflex	119.00	185.50°	-72.10°	Non	Reflex	218.00	188.50°	-67.60°	Non
Reflex	122.00	185.70°	-72.00°	Non	Reflex	221.00	188.60°	-67.30°	Non
Reflex	125.00	185.40°	-71.90°	Non	Reflex	224.00	189.10°	-67.10°	Non
Reflex	128.00	185.50°	-71.80°	Non	Reflex	227.00	189.20°	-66.80°	Non
Reflex	131.00	186.00°	-71.60°	Non	Reflex	230.00	189.10°	-66.60°	Non
Reflex	134.00	186.00°	-71.50°	Non	Reflex	233.00	189.50°	-66.30°	Non
Reflex	137.00	186.50°	-71.40°	Non	Reflex	236.00	189.50°	-66.10°	Non
Reflex	140.00	187.10°	-71.40°	Non	Reflex	239.00	189.80°	-65.90°	Non
Reflex	143.00	187.30°	-71.30°	Non	Reflex	242.00	189.80°	-65.90°	Non
Reflex	146.00	187.80°	-71.20°	Non	Reflex	245.00	189.10°	-65.70°	Non
Reflex	149.00	187.60°	-71.20°	Non	Reflex	248.00	188.20°	-65.50°	Non
Reflex	152.00	188.10°	-71.10°	Non	Reflex	251.00	188.40°	-65.10°	Non
Reflex	155.00	188.20°	-71.00°	Non	Reflex	254.00	187.80°	-64.90°	Non
Reflex	158.00	188.50°	-70.90°	Non	Reflex	257.00	186.90°	-64.90°	Non
Reflex	161.00	188.30°	-70.80°	Non	Reflex	260.00	186.80°	-64.90°	Non
Reflex	164.00	188.50°	-70.60°	Non	Reflex	263.00	186.70°	-64.90°	Non
Reflex	167.00	188.20°	-70.50°	Non	Reflex	266.00	186.50°	-65.00°	Non
Reflex	170.00	188.40°	-70.30°	Non	Reflex	269.00	186.50°	-64.80°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	186.50°	-64.70°	Non					
Reflex	275.00	186.20°	-64.70°	Non					
Reflex	278.00	186.10°	-64.60°	Non					
Reflex	281.00	186.10°	-64.60°	Non					
Reflex	284.00	186.20°	-64.50°	Non					
Reflex	287.00	185.90°	-64.50°	Non					
Reflex	290.00	185.80°	-64.50°	Non					
Reflex	293.00	185.50°	-64.60°	Non					
Reflex	296.00	185.60°	-64.50°	Non					
Reflex	299.00	185.10°	-64.60°	Non					
Reflex	302.00	184.90°	-64.60°	Non					
Reflex	305.00	184.60°	-64.50°	Non					
Reflex	308.00	184.30°	-64.40°	Non					
Reflex	311.00	184.20°	-64.30°	Non					
Reflex	314.00	184.40°	-64.20°	Non					
Reflex	317.00	184.50°	-64.10°	Non					
Reflex	320.00	184.20°	-64.10°	Non					
Reflex	323.00	184.20°	-64.00°	Non					
Reflex	326.00	184.30°	-64.00°	Non					
Reflex	328.10	184.30°	-63.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	7.30	MT <b>Mort-terrain</b>						
7.30	101.00	SY <b>Syénite</b> Generally reddish grey, locally greenish grey, overall massive with no bedding evident. Local zones of intense carbonatization and hematitization, as well as sericitization. Increase in sericitization and mineralization towards lower contact.	7.30	9.00	D016001	1.70	0.107	0.107
			9.00	10.50	D016002	1.50	<0.005	0.001
			10.50	12.00	D016003	1.50	<0.005	0.001
			12.00	13.50	D016005	1.50	0.007	0.007
			13.50	15.00	D016006	1.50	<0.005	0.001
			15.00	16.50	D016007	1.50	<0.005	0.001
			16.50	18.00	D016008	1.50	0.006	0.006
			18.00	19.50	D016009	1.50	<0.005	0.001
			19.50	21.00	D016010	1.50	<0.005	0.001
			21.00	22.00	D016011	1.00	0.011	0.011
			22.00	23.00	D016012	1.00	0.017	0.017
			23.00	24.00	D016013	1.00	<0.005	0.001
			24.00	25.50	D016015	1.50	<0.005	0.001
			25.50	27.00	D016016	1.50	<0.005	0.001
			27.00	28.50	D016017	1.50	<0.005	0.001
			28.50	30.00	D016018	1.50	0.005	0.005
			30.00	31.50	D016019	1.50	0.210	0.210
			31.50	33.00	D016020	1.50	0.492	0.492
			33.00	34.50	D016021	1.50	0.398	0.398
			34.50	36.00	D016022	1.50	0.333	0.333
			36.00	37.50	D016023	1.50	0.648	0.648
			37.50	39.00	D016025	1.50	1.245	1.245
			39.00	40.50	D016026	1.50	0.048	0.048
			40.50	42.00	D016027	1.50	0.013	0.013
			42.00	43.50	D016028	1.50	0.665	0.665
			43.50	45.00	D016029	1.50	0.890	0.890
			45.00	46.50	D016030	1.50	2.520	2.520
			46.50	48.00	D016031	1.50	0.008	0.008
			48.00	49.50	D016032	1.50	0.148	0.148
			49.50	51.00	D016033	1.50	0.462	0.462
			51.00	52.50	D016035	1.50	2.650	2.650

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
7.30	100.00	SY; POR; MOY <b>Syérite; Porphyrique; Grains moyens</b> Overall medium grained, with local zones of coarser and finer phenocrysts. Phenocrysts range in size from <1mm up to ++10mm. Phenocrysts are generally subhedral to euhedral. Veins/veinlets are generally randomly oriented.	52.50	54.00	D016036	1.50	0.045		0.045
			54.00	55.50	D016037	1.50	0.434		0.434
			55.50	57.00	D016038	1.50	0.706		0.706
			57.00	58.50	D016039	1.50	0.058		0.058
			58.50	60.00	D016040	1.50	0.017		0.017
			60.00	61.50	D016041	1.50	0.007		0.007
			61.40	61.50	FAI <b>Faille</b> broken, rubbled, minor gouge. Upper contact @ 36 dtca, lower contact @ 38 dtca. Contacts are both slickesided.	61.50	63.00	D016042	1.50
63.00	64.50	D016043				1.50	0.052		0.052
64.50	66.00	D016045				1.50	0.005		0.005
66.00	67.50	D016046				1.50	0.270		0.270
67.50	69.00	D016047				1.50	1.395		1.395
69.00	70.50	D016048				1.50	0.065		0.065
70.50	72.00	D016049				1.50	0.128		0.128
72.00	73.50	D016050				1.50	0.009		0.009
73.50	75.00	D016051				1.50	<0.005		0.001
75.00	76.50	D016052				1.50	0.024		0.024
76.50	78.00	D016053				1.50	<0.005		0.001
78.00	79.50	D016055				1.50	<0.005		0.001
79.50	81.00	D016056				1.50	0.006		0.006
81.00	82.50	D016057				1.50	<0.005		0.001
82.50	84.00	D016058				1.50	0.045		0.045
84.00	85.50	D016059				1.50	<0.005		0.001
85.50	87.00	D016060				1.50	<0.005		0.001
87.00	88.00	D016061				1.00	0.005		0.005
88.00	94.00	CIS <b>Cisaillement</b> Weakly developed shear zone with local stronger shearing. Parallel fracturing when present is at 42-52 DTCA. Zone is also strongly sericitized, with minor silicification.				88.00	89.50	D016062	1.50
			89.50	90.80	D016063	1.30	0.451		0.451
			90.80	92.50	D016065	1.70	0.127		0.127
			92.50	94.00	D016066	1.50	0.628		0.628



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
101.00	116.00	MS  <b>Mudstone</b> Massive with local weak laminations. Overall dark grey to black. Very fragmental and broken up. Contacts are not distinct. Upper contact is in broken core, while lower contact appears to be gradational with tuff unit below (???)	94.00	95.50	D016067	1.50	2.800	5.59 3.47	2.800
			95.50	97.00	D016068	1.50	5.430		5.590
			97.00	98.50	D016069	1.50	3.410		3.470
			98.50	100.00	D016070	1.50	2.360		2.360
			100.00	101.00	D016071	1.00	1.770		1.770
			101.00	102.50	D016072	1.50	2.240		2.240
			102.50	104.00	D016073	1.50	0.377		0.377
			104.00	105.50	D016075	1.50	1.700		1.700
			105.50	107.00	D016076	1.50	1.545		1.545
			107.00	108.50	D016077	1.50	0.800		0.800
			108.50	110.00	D016078	1.50	1.770		1.770
			110.00	111.30	D016079	1.30	0.702		0.702
			111.30	113.00	D016080	1.70	0.932		0.932
			113.00	114.50	D016081	1.50	0.005		0.005
116.00	123.08	TU; FIN; LAM  <b>Tuf mafique; Grains fins; Laminations parallèles</b> Fine grained, weakly laminated, chloritized tuff. Minor sericite and silicate overprinting. Laminations are sub perpendicular to core axis. Greyish green in colour.	114.50	116.00	D016082	1.50	<0.005	0.001	
			116.00	117.00	D016083	1.00	<0.005	0.001	
			117.00	118.50	D016085	1.50	<0.005	0.001	
			118.50	120.00	D016086	1.50	<0.005	0.001	
			120.00	121.50	D016087	1.50	0.026	0.026	
			121.50	123.00	D016088	1.50	6.620	6.78	6.780
123.08	126.65	SY; PT  <b>Syénite; Porphyre trachytique</b> Trachytic syenite porphyry with 0.5mm- +20mm phenocrysts. Weak alignment present at 38 dtca. Upper contact is broken and rubbled. Lower contact is sharp at 40 dtca.	123.00	124.50	D016089	1.50	1.735	1.735	
			124.50	125.60	D016090	1.10	0.046	0.046	
			125.60	126.60	D016091	1.00	1.050	1.050	
			126.60	128.00	D016092	1.40	0.036	0.036	
126.65	137.50	TU; LAM  <b>Tuf mafique; Laminations parallèles</b> Similar to unit from 116.00-123.08, though this unit is has well defined laminations. Laminae are at 50 dtca. Overall colour is olive green to dark grey-green. Tuff is fine to locally very fine grained. Also has interbedded sediments - STST and MDST.	128.00	129.50	D016093	1.50	0.683	0.683	
			129.50	131.00	D016095	1.50	<0.005	0.001	
			131.00	132.50	D016096	1.50	<0.005	0.001	
			132.50	134.00	D016097	1.50	<0.005	0.001	
			134.00	135.50	D016098	1.50	<0.005	0.001	
			135.50	136.50	D016099	1.00	0.273	0.273	
137.50	140.30	MS; ST; LAM	136.50	137.50	D016100	1.00	<0.005	0.001	
			137.50	139.00	D016101	1.50	0.047	0.047	

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
140.30	245.60	<b>Mudstone; Siltstone; Laminations parallèles</b>						
		Interbedded mudstone/siltstone, with laminations @ 60-70 DTCA. Graphite common on fracture surfaces. Upper contact is sharp @ 65 DTCA. Lower contact is irregular.						
		TU; LAM						
		<b>Tuf mafique; Laminations parallèles</b>						
		Similar to unit from 116.00-123.08, though this unit is has well defined laminations - laminae angles and sizes variable, though generally angles are 30-60 DTCA, and laminae are 1-10mm thick. Overall colour is olive green to dark grey-green. Tuff is fine to locally very fine grained, with rare coarser zones. Also has interbedded sediments - STST and MDST - contain graphitic layers. Strongly chloritized / sericitized - chlorite may also contain silica Moderate to strong foliation present, as well as local shearing. Unit has black, hard layers throughout - though to be highly indurated mudstone or silicified chlorite - possibly tourmaline. Local calcite flooding of matrix. Tuff is also rarely locally fragmental.						
		139.00	140.30	D016102	1.30	0.310		0.310
		140.30	142.00	D016103	1.70	2.870		2.870
		142.00	143.50	D016105	1.50	0.014		0.014
		143.50	145.00	D016106	1.50	0.007		0.007
		145.00	146.50	D016107	1.50	<0.005		0.001
		146.50	148.00	D016108	1.50	0.005		0.005
		148.00	149.50	D016109	1.50	0.005		0.005
		149.50	151.00	D016110	1.50	<0.005		0.001
		151.00	152.50	D016111	1.50	<0.005		0.001
		152.50	154.00	D016112	1.50	<0.005		0.001
		154.00	155.50	D016113	1.50	<0.005		0.001
		155.50	157.00	D016115	1.50	<0.005		0.001
		157.00	158.50	D016116	1.50	0.011		0.011
		158.50	160.00	D016117	1.50	<0.005		0.001
		160.00	161.50	D016118	1.50	<0.005		0.001
		161.50	163.00	D016119	1.50	<0.005		0.001
		163.00	164.50	D016120	1.50	<0.005		0.001
		164.50	166.00	D016121	1.50	<0.005		0.001
		166.00	167.50	D016122	1.50	<0.005		0.001
167.50	169.00	D016123	1.50	<0.005		0.001		
169.00	170.50	D016125	1.50	<0.005		0.001		
170.50	172.00	D016126	1.50	<0.005		0.001		
172.00	173.50	D016127	1.50	<0.005		0.001		
173.50	174.80	D016128	1.30	<0.005		0.001		
174.80	176.00	D016129	1.20	<0.005		0.001		
176.00	177.50	D016130	1.50	0.005		0.005		
177.50	179.00	D016131	1.50	<0.005		0.001		
179.00	180.50	D016132	1.50	<0.005		0.001		
180.50	182.00	D016133	1.50	<0.005		0.001		
182.00	183.50	D016135	1.50	<0.005		0.001		
183.50	185.00	D016136	1.50	<0.005		0.001		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	185.00	186.50	D016137	1.50	<0.005		0.001
	186.50	188.00	D016138	1.50	<0.005		0.001
	188.00	189.50	D016139	1.50	<0.005		0.001
	189.50	191.00	D016140	1.50	0.089		0.089
	191.00	192.50	D016141	1.50	0.567		0.567
	192.50	194.00	D016142	1.50	0.486		0.486
	194.00	195.50	D016143	1.50	1.050		1.050
	195.50	197.00	D016145	1.50	0.331		0.331
	197.00	198.50	D016146	1.50	0.437		0.437
	198.50	200.00	D016147	1.50	0.289		0.289
	200.00	201.50	D016148	1.50	1.105		1.105
	201.50	203.00	D016149	1.50	0.364		0.364
	203.00	204.50	D016150	1.50	0.303		0.303
	204.50	206.00	D016151	1.50	0.421		0.421
	206.00	207.50	D016152	1.50	0.512		0.512
	207.50	209.00	D016153	1.50	0.471		0.471
	209.00	210.50	D016155	1.50	0.485		0.485
	210.50	212.00	D016156	1.50	0.358		0.358
	212.00	213.50	D016157	1.50	0.426		0.426
	213.50	215.00	D016158	1.50	0.856		0.856
	215.00	216.50	D016159	1.50	0.498		0.498
	216.50	218.00	D016160	1.50	0.378		0.378
	218.00	219.50	D016161	1.50	0.006		0.006
	219.50	221.00	D016162	1.50	<0.005		0.001
	221.00	222.50	D016163	1.50	<0.005		0.001
	222.50	224.00	D016165	1.50	<0.005		0.001
	224.00	225.50	D016166	1.50	<0.005		0.001
	225.50	227.00	D016167	1.50	<0.005		0.001
	227.00	228.50	D016168	1.50	<0.005		0.001
	228.50	230.00	D016169	1.50	<0.005		0.001
	230.00	231.50	D016170	1.50	<0.005		0.001
	231.50	233.00	D016171	1.50	<0.005		0.001
	233.00	234.50	D016172	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
245.60	305.80	UM; LAM; UM <b>Ultramaïte serpentinisée; Laminations parallèles; Komatiite</b> Dark green - black, talc-carbonate rich, weakly schistose ultramafics - possibly Komatiite. Unit has overall abundant cc with lesser qtz, though local zones of decreased concentration are present. Strong deformation present throughout. Locally brecciated with fragments up to 7cm - possibly flow related. Lamination angles vary due to deformation. Upper contact is marked by a qtz vein @ 70 DTCA. Localized spinifex texture. Local zones of intermixed pyroclastics.	234.50	236.00	D016173	1.50	<0.005		0.001
			236.00	237.50	D016175	1.50	0.027		0.027
			237.50	238.60	D016176	1.10	0.101		0.101
			238.60	240.30	D016177	1.70	<0.005		0.001
			240.30	241.40	D016178	1.10	0.036		0.036
			241.40	243.00	D016179	1.60	<0.005		0.001
			243.00	244.50	D016180	1.50	<0.005		0.001
			244.50	245.60	D016181	1.10	0.005		0.005
			245.60	247.30	D016182	1.70	<0.005		0.001
			247.30	249.00	D016183	1.70	<0.005		0.001
			249.00	250.50	D016185	1.50	<0.005		0.001
			250.50	252.00	D016186	1.50	<0.005		0.001
			252.00	253.50	D016187	1.50	<0.005		0.001
			253.50	255.00	D016188	1.50	<0.005		0.001
			255.00	256.50	D016189	1.50	<0.005		0.001
			256.50	258.00	D016190	1.50	<0.005		0.001
			258.00	259.50	D016191	1.50	<0.005		0.001
			259.50	261.00	D016192	1.50	<0.005		0.001
			261.00	262.50	D016193	1.50	<0.005		0.001
			262.50	264.00	D016195	1.50	<0.005		0.001
			264.00	265.50	D016196	1.50	<0.005		0.001
			265.50	267.00	D016197	1.50	<0.005		0.001
			267.00	268.50	D016198	1.50	<0.005		0.001
			268.50	270.00	D016199	1.50	<0.005		0.001
			270.00	271.50	D016200	1.50	0.018		0.018
			271.50	273.00	D016201	1.50	0.005		0.005
			273.00	274.50	D016202	1.50	<0.005		0.001
			274.50	276.00	D016203	1.50	<0.005		0.001
276.00	277.50	D016205	1.50	0.670		0.670			
277.50	279.00	D016206	1.50	0.006		0.006			
279.00	280.50	D016207	1.50	<0.005		0.001			
280.50	282.00	D016208	1.50	<0.005		0.001			
282.00	283.50	D016209	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				283.50	285.00	D016210	1.50	<0.005		0.001
				285.00	286.50	D016211	1.50	<0.005		0.001
				286.50	288.00	D016212	1.50	<0.005		0.001
				288.00	289.50	D016213	1.50	<0.005		0.001
				289.50	291.00	D016215	1.50	<0.005		0.001
				291.00	292.50	D016216	1.50	<0.005		0.001
				292.50	294.00	D016217	1.50	<0.005		0.001
				294.00	295.50	D016218	1.50	<0.005		0.001
				295.50	297.00	D016219	1.50	<0.005		0.001
				297.00	298.50	D016220	1.50	<0.005		0.001
				298.50	300.00	D016221	1.50	<0.005		0.001
				300.00	301.50	D016222	1.50	<0.005		0.001
300.48	300.55	FAI		301.50	303.00	D016223	1.50	<0.005		0.001
		<b>Faïlle</b>		303.00	304.40	D016225	1.40	<0.005		0.001
		Broken, rubbled, gouge filled. Upper contact is approx 90 DTCA, while lower ct is @ 60 DTCA.								
303.13	303.20	FAI		304.40	305.80	D016226	1.40	<0.005		0.001
		<b>Faïlle</b>								
		broken, rubbled, gouge filled. Upper and lower contacts are at approx 42 DTCA.								
305.80	309.03	MS; ST; LAM		305.80	307.40	D016227	1.60	<0.005		0.001
		<b>Mudstone; Siltstone; Laminations parallèles</b>								
		Highly laminated and foliated sediments - mix of indurated mudstone and siltstone. Laminations have been strongly deformed. Angles range from sub-parallel to 70 DTCA. Upper contact is sharp and marked by a fracture @ approx 20 DTCA. Sediment are black in colour.								
307.00	307.07	FAI		307.40	309.00	D016228	1.60	0.010		0.010
		<b>Faïlle</b>		309.00	310.50	D016229	1.50	<0.005		0.001
		broken, rubbled, gouge filled. Upper and lower contacts @ approx 50 DTCA.								
309.03	321.20	TU; LAM		310.50	312.00	D016230	1.50	<0.005		0.001
		<b>Tuf mafique; Laminations parallèles</b>		312.00	313.50	D016231	1.50	<0.005		0.001
		Laminated fg tuff. Olive green to dark green in colour. Laminations are @ 40 DTCA. upper contact is sharp @ 42 DTCA. Moderate deformation of layering proximal to upper contact. Lower 3-4m has intermixed ultramafics from unit below, suggesting a syndepositional environment or slumping.		313.50	315.00	D016232	1.50	<0.005		0.001
				315.00	316.50	D016233	1.50	<0.005		0.001
				316.50	318.00	D016235	1.50	<0.005		0.001
				318.00	319.50	D016236	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
321.20	328.10	UM; LAM; UM <b>Ultramaïte serpentinisée; Laminations parallèles; Komatiite</b> Dark green - black, talc-carbonate rich, weakly schistose ultramafics - possibly Komatiite - continuation of ultramafic unit from 245.6-305.8m. Unit has overall abundant cc with lesser qtz, though local zones of decreased concentration are present. Strong deformation present throughout. Locally brecciated with fragments up to 10cm - possibly flow related. Lamination angles vary due to deformation.	319.50	321.20	D016237	1.70	<0.005		0.001
			321.20	322.60	D016238	1.40	<0.005		0.001
			322.60	324.00	D016239	1.40	<0.005		0.001
			324.00	325.50	D016240	1.50	<0.005		0.001
			325.50	327.00	D016241	1.50	<0.005		0.001
			327.00	328.10	D016242	1.10	<0.005		0.001
330.00	Fin du sondage Nombre d'échantillons : 218 Nombre d'échantillons QAQC : 24 Longueur totale échantillonnée : 320.80								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.50	12.00	D016004	D016003	1.50	<0.005	0.001
23.00	23.00	D016014	A3	0.00	0.599	0.599
36.00	37.50	D016024	D016023	1.50	0.898	0.898
49.50	49.50	D016034	M1	0.00	<0.005	0.001
63.00	64.50	D016044	D016043	1.50	0.049	0.049
76.50	76.50	D016054	B4	0.00	2.530	2.530
89.50	90.80	D016064	D016063	1.30	0.505	0.505
102.50	102.50	D016074	M1	0.00	<0.005	0.001
116.00	117.00	D016084	D016083	1.00	<0.005	0.001
128.00	128.00	D016094	C4	0.00	1.310	1.310
140.30	142.00	D016104	D016103	1.70	3.030	3.140
154.00	154.00	D016114	M1	0.00	<0.005	0.001
167.50	169.00	D016124	D016123	1.50	<0.005	0.001
180.50	180.50	D016134	D2	0.00	0.849	0.849
194.00	195.50	D016144	D016143	1.50	1.110	1.110
207.50	207.50	D016154	M1	0.00	<0.005	0.001
221.00	222.50	D016164	D016163	1.50	<0.005	0.001
234.50	234.50	D016174	F2	0.00	8.520	8.450
247.30	249.00	D016184	D016183	1.70	<0.005	0.001
261.00	261.00	D016194	M1	0.00	<0.005	0.001
274.50	276.00	D016204	D016203	1.50	<0.005	0.001
288.00	288.00	D016214	G2	0.00	4.120	4.060
301.50	303.00	D016224	D016223	1.50	<0.005	0.001
315.00	315.00	D016234	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-144**

Titre minier :

Section :                      630700

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              bradley

Lot :

Décrit par :          David Ruhara

Du :                      2010-03-15

Date de description :      2010-04-15

Au :                      2010-03-21

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            491.00 m

Est	630 699.7
Nord	5 374 400.0
Élévation	308.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	74.80°	-60.60°	Oui
Reflex	5.00	354.80°	-60.30°	Oui
Reflex	8.00	355.90°	-60.60°	Oui
Reflex	11.00	355.80°	-60.00°	Oui
Reflex	14.00	358.50°	-60.30°	Non
Reflex	17.00	359.10°	-60.30°	Non
Reflex	20.00	359.30°	-60.30°	Non
Reflex	23.00	0.60°	-60.20°	Non
Reflex	26.00	360.00°	-60.20°	Non
Reflex	29.00	0.80°	-60.10°	Non
Reflex	32.00	359.50°	-60.00°	Non
Reflex	35.00	359.30°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.00°	-60.00°	Non
Reflex	41.00	359.70°	-60.10°	Non
Reflex	44.00	1.80°	-60.00°	Oui
Reflex	47.00	0.70°	-59.90°	Non
Reflex	50.00	359.00°	-59.70°	Non
Reflex	53.00	357.20°	-59.60°	Non
Reflex	56.00	357.00°	-59.70°	Non
Reflex	59.00	356.90°	-60.00°	Non
Reflex	62.00	358.50°	-60.00°	Non
Reflex	65.00	359.20°	-59.90°	Non
Reflex	68.00	358.30°	-59.90°	Non
Reflex	71.00	357.80°	-59.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.80°	-59.80°	Non	Reflex	173.00	0.00°	-58.80°	Non
Reflex	77.00	359.00°	-59.80°	Non	Reflex	176.00	0.00°	-58.70°	Non
Reflex	80.00	358.00°	-59.80°	Non	Reflex	179.00	360.00°	-58.70°	Non
Reflex	83.00	357.00°	-59.80°	Non	Reflex	182.00	0.10°	-58.70°	Non
Reflex	86.00	359.20°	-59.70°	Non	Reflex	185.00	0.00°	-58.60°	Non
Reflex	89.00	0.00°	-59.70°	Non	Reflex	188.00	0.00°	-58.50°	Non
Reflex	92.00	0.00°	-59.70°	Non	Reflex	191.00	359.90°	-58.50°	Non
Reflex	95.00	359.00°	-59.70°	Non	Reflex	194.00	360.00°	-58.60°	Non
Reflex	98.00	0.00°	-59.70°	Non	Reflex	197.00	0.20°	-58.60°	Non
Reflex	101.00	358.50°	-59.80°	Non	Reflex	200.00	0.10°	-58.60°	Non
Reflex	104.00	0.50°	-59.80°	Non	Reflex	203.00	0.10°	-58.60°	Non
Reflex	107.00	1.30°	-59.80°	Oui	Reflex	206.00	0.10°	-58.50°	Non
Reflex	110.00	0.30°	-59.70°	Non	Reflex	209.00	359.90°	-58.50°	Non
Reflex	113.00	1.40°	-59.70°	Non	Reflex	212.00	0.00°	-58.50°	Non
Reflex	116.00	1.40°	-59.70°	Non	Reflex	215.00	0.00°	-58.60°	Non
Reflex	119.00	1.50°	-59.70°	Non	Reflex	218.00	0.10°	-58.60°	Non
Reflex	122.00	1.60°	-59.70°	Non	Reflex	221.00	0.10°	-58.60°	Non
Reflex	125.00	1.00°	-59.70°	Non	Reflex	224.00	0.30°	-58.70°	Non
Reflex	128.00	0.60°	-59.60°	Non	Reflex	227.00	0.30°	-58.70°	Non
Reflex	131.00	1.70°	-59.70°	Non	Reflex	230.00	0.50°	-58.70°	Non
Reflex	134.00	0.70°	-59.60°	Non	Reflex	233.00	0.40°	-58.70°	Non
Reflex	137.00	1.20°	-59.70°	Non	Reflex	236.00	0.40°	-58.70°	Non
Reflex	140.00	1.20°	-59.70°	Non	Reflex	239.00	0.20°	-58.60°	Non
Reflex	143.00	1.10°	-59.70°	Non	Reflex	242.00	0.20°	-58.60°	Non
Reflex	146.00	1.40°	-59.70°	Non	Reflex	245.00	0.20°	-58.70°	Non
Reflex	149.00	0.70°	-59.70°	Non	Reflex	248.00	0.20°	-58.70°	Non
Reflex	152.00	0.50°	-59.60°	Non	Reflex	251.00	0.30°	-58.70°	Non
Reflex	155.00	0.30°	-59.30°	Non	Reflex	254.00	0.30°	-58.80°	Non
Reflex	158.00	359.90°	-59.00°	Non	Reflex	257.00	0.50°	-58.80°	Non
Reflex	161.00	359.80°	-58.80°	Non	Reflex	260.00	0.50°	-58.80°	Non
Reflex	164.00	359.80°	-58.80°	Non	Reflex	263.00	0.60°	-58.80°	Non
Reflex	167.00	359.90°	-58.80°	Non	Reflex	266.00	0.70°	-58.90°	Non
Reflex	170.00	359.90°	-58.80°	Non	Reflex	269.00	0.70°	-58.90°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	0.80°	-58.80°	Non
Reflex	275.00	1.00°	-58.80°	Non
Reflex	278.00	1.00°	-58.90°	Non
Reflex	281.00	1.10°	-58.80°	Non
Reflex	284.00	1.30°	-58.90°	Non
Reflex	287.00	1.50°	-59.00°	Non
Reflex	290.00	1.60°	-59.00°	Non
Reflex	293.00	1.70°	-59.00°	Non
Reflex	296.00	1.60°	-59.00°	Non
Reflex	299.00	1.80°	-59.00°	Non
Reflex	302.00	3.30°	-58.90°	Oui
Reflex	305.00	2.90°	-58.80°	Non
Reflex	308.00	2.80°	-58.90°	Non
Reflex	311.00	2.80°	-58.90°	Non
Reflex	314.00	2.80°	-59.00°	Non
Reflex	317.00	3.00°	-59.00°	Non
Reflex	320.00	3.00°	-58.80°	Non
Reflex	323.00	3.20°	-58.80°	Non
Reflex	326.00	3.30°	-58.80°	Non
Reflex	329.00	3.30°	-58.70°	Non
Reflex	332.00	3.40°	-58.70°	Non
Reflex	335.00	3.00°	-58.70°	Non
Reflex	338.00	2.70°	-58.70°	Oui
Reflex	341.00	4.60°	-58.70°	Non
Reflex	344.00	2.50°	-58.70°	Oui
Reflex	347.00	3.80°	-58.70°	Non
Reflex	350.00	3.90°	-58.60°	Non
Reflex	353.00	3.80°	-58.60°	Non
Reflex	356.00	3.60°	-58.70°	Non
Reflex	359.00	3.10°	-58.70°	Non
Reflex	362.00	4.80°	-58.60°	Non
Reflex	365.00	4.50°	-58.60°	Non
Reflex	368.00	4.40°	-58.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	5.20°	-58.60°	Oui
Reflex	374.00	4.20°	-58.60°	Non
Reflex	377.00	4.40°	-58.60°	Non
Reflex	380.00	4.70°	-58.50°	Non
Reflex	383.00	4.20°	-58.50°	Non
Reflex	386.00	3.50°	-58.50°	Non
Reflex	389.00	3.80°	-58.60°	Non
Reflex	392.00	4.00°	-58.60°	Non
Reflex	395.00	5.10°	-58.60°	Oui
Reflex	398.00	4.60°	-58.60°	Non
Reflex	401.00	5.00°	-58.50°	Non
Reflex	404.00	4.90°	-58.50°	Non
Reflex	407.00	5.00°	-58.50°	Non
Reflex	410.00	4.90°	-58.40°	Non
Reflex	413.00	4.90°	-58.30°	Non
Reflex	416.00	5.00°	-58.30°	Non
Reflex	419.00	5.00°	-58.20°	Non
Reflex	422.00	5.20°	-58.30°	Non
Reflex	425.00	5.20°	-58.20°	Non
Reflex	428.00	5.10°	-58.10°	Non
Reflex	431.00	5.20°	-58.00°	Non
Reflex	434.00	5.20°	-57.90°	Non
Reflex	437.00	5.10°	-57.70°	Non
Reflex	440.00	5.20°	-57.70°	Non
Reflex	443.00	5.20°	-57.60°	Non
Reflex	446.00	5.20°	-57.40°	Non
Reflex	449.00	5.20°	-57.30°	Non
Reflex	452.00	5.30°	-57.30°	Non
Reflex	455.00	5.30°	-57.20°	Non
Reflex	458.00	5.40°	-57.20°	Non
Reflex	461.00	5.50°	-57.20°	Non
Reflex	464.00	5.50°	-57.20°	Non
Reflex	467.00	5.60°	-57.10°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	5.70°	-57.10°	Non
Reflex	473.00	5.90°	-57.00°	Non
Reflex	476.00	5.90°	-57.00°	Non
Reflex	479.00	6.10°	-57.00°	Non
Reflex	482.00	6.30°	-57.00°	Non
Reflex	485.00	6.30°	-56.90°	Non
Reflex	488.00	6.50°	-57.00°	Non
Reflex	491.00	6.80°	-57.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT						
		<b>Mort-terrain</b>						
2.50	141.00	SY; POR	2.50	4.00	D006035	1.50	<0.005	0.001
		<b>Syénite; Porphyrique</b>						
		Syénite porphyrique à phénocristaux à tendance Xmm à rarement Xcm	4.00	5.50	D006036	1.50	<0.005	0.001
		et à quantité variable. Qlq veines et veinules de CB reparti	5.50	7.00	D006038	1.50	<0.005	0.001
		irrégulièrement et qlq rare VQZ. MG++ différenciellement.	7.00	8.50	D006039	1.50	<0.005	0.001
			8.50	10.00	D006040	1.50	<0.005	0.001
			10.00	11.50	D006041	1.50	<0.005	0.001
			11.50	13.00	D006043	1.50	<0.005	0.001
			13.00	14.50	D006044	1.50	<0.005	0.001
			14.50	16.00	D006045	1.50	<0.005	0.001
			16.00	17.50	D006046	1.50	<0.005	0.001
			17.50	19.00	D006048	1.50	<0.005	0.001
			19.00	20.50	D006049	1.50	<0.005	0.001
			20.50	22.00	D006050	1.50	<0.005	0.001
			22.00	23.50	D006051	1.50	<0.005	0.001
			23.50	25.00	D006052	1.50	<0.005	0.001
			25.00	26.50	D006053	1.50	<0.005	0.001
			26.50	28.00	D006054	1.50	<0.005	0.001
			28.00	29.50	D006055	1.50	<0.005	0.001
			29.50	31.00	D006056	1.50	0.010	0.010
			31.00	32.50	D006058	1.50	<0.005	0.001
			32.50	34.00	D006059	1.50	0.073	0.073
			34.00	35.50	D006060	1.50	0.016	0.016
			35.50	37.00	D006061	1.50	<0.005	0.001
			37.00	38.50	D006062	1.50	0.155	0.155
			38.50	40.00	D006063	1.50	0.030	0.030
			40.00	41.50	D006064	1.50	0.172	0.172
			41.50	43.00	D006065	1.50	0.049	0.049
			43.00	44.50	D006066	1.50	0.169	0.169
			44.50	46.00	D006068	1.50	<0.005	0.001
			46.00	47.50	D006069	1.50	0.029	0.029
			47.50	49.00	D006070	1.50	0.018	0.018
			49.00	50.50	D006071	1.50	0.019	0.019

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.50	52.00	D006072	1.50	0.051		0.051
	52.00	53.50	D006073	1.50	<0.005		0.001
	53.50	55.00	D006074	1.50	0.071		0.071
	55.00	56.50	D006075	1.50	0.018		0.018
	56.50	58.00	D006076	1.50	0.008		0.008
	58.00	59.50	D006078	1.50	0.012		0.012
	59.50	61.00	D006079	1.50	0.021		0.021
	61.00	62.50	D006080	1.50	0.270		0.270
	62.50	64.00	D006081	1.50	0.754		0.754
	64.00	65.50	D006083	1.50	0.225		0.225
	65.50	67.00	D006084	1.50	<0.005		0.001
	67.00	68.50	D006085	1.50	0.098		0.098
	68.50	70.00	D006086	1.50	0.034		0.034
	70.00	71.50	D006088	1.50	0.305		0.305
	71.50	73.00	D006089	1.50	<0.005		0.001
	73.00	74.50	D006090	1.50	<0.005		0.001
	74.50	76.00	D006091	1.50	<0.005		0.001
	76.00	77.50	D006092	1.50	<0.005		0.001
	77.50	79.00	D006093	1.50	<0.005		0.001
	79.00	80.50	D006094	1.50	<0.005		0.001
	80.50	82.00	D006095	1.50	<0.005		0.001
	82.00	83.50	D006096	1.50	<0.005		0.001
	83.50	85.00	D006098	1.50	0.023		0.023
	85.00	86.50	D006099	1.50	<0.005		0.001
	86.50	88.00	D006100	1.50	<0.005		0.001
	88.00	89.50	D006101	1.50	<0.005		0.001
	89.50	91.00	D006102	1.50	0.030		0.030
	91.00	92.50	D006103	1.50	<0.005		0.001
	92.50	93.90	D006104	1.40	0.013		0.013
	93.90	95.50	D006105	1.60	0.254		0.254
	95.50	97.00	D006106	1.50	0.891		0.891
	97.00	98.50	D006108	1.50	0.651		0.651
	98.50	100.00	D006109	1.50	0.350		0.350



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.50	150.00	D006148	1.50	<0.005		0.001
	150.00	151.50	D006149	1.50	<0.005		0.001
	151.50	153.00	D006150	1.50	<0.005		0.001
	153.00	154.50	D006151	1.50	<0.005		0.001
	154.50	156.00	D006152	1.50	<0.005		0.001
	156.00	157.50	D006153	1.50	0.157		0.157
	157.50	159.00	D006154	1.50	<0.005		0.001
	159.00	160.50	D006155	1.50	<0.005		0.001
	160.50	162.00	D006156	1.50	<0.005		0.001
	162.00	163.50	D006158	1.50	<0.005		0.001
	163.50	165.00	D006159	1.50	<0.005		0.001
	165.00	166.50	D006160	1.50	<0.005		0.001
	166.50	168.00	D006161	1.50	<0.005		0.001
	168.00	169.50	D006163	1.50	0.008		0.008
	169.50	171.00	D006164	1.50	0.022		0.022
	171.00	172.50	D006165	1.50	0.024		0.024
	172.50	174.00	D006166	1.50	0.071		0.071
	174.00	175.50	D006168	1.50	<0.005		0.001
	175.50	177.00	D006169	1.50	0.006		0.006
	177.00	178.50	D006170	1.50	3.320		3.320
	178.50	180.00	D006171	1.50	0.679		0.679
	180.00	181.50	D006172	1.50	0.972		0.972
	181.50	183.00	D006173	1.50	0.019		0.019
	183.00	184.50	D006174	1.50	0.070		0.070
	184.50	186.00	D006175	1.50	<0.005		0.001
	186.00	187.50	D006176	1.50	<0.005		0.001
	187.50	189.00	D006178	1.50	<0.005		0.001
	189.00	190.50	D006179	1.50	<0.005		0.001
	190.50	192.00	D006180	1.50	0.007		0.007
	192.00	193.50	D006181	1.50	0.132		0.132
	193.50	195.00	D006182	1.50	0.204		0.204
	195.00	196.50	D006183	1.50	0.097		0.097
	196.50	198.00	D006184	1.50	0.405		0.405

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	198.00	199.50	D006185	1.50	0.074		0.074
	199.50	201.00	D006186	1.50	0.237		0.237
	201.00	202.50	D006188	1.50	<0.005		0.001
	202.50	204.00	D006189	1.50	<0.005		0.001
	204.00	205.50	D006190	1.50	0.013		0.013
	205.50	207.00	D006191	1.50	0.009		0.009
	207.00	208.50	D006192	1.50	0.011		0.011
	208.50	210.00	D006193	1.50	0.007		0.007
	210.00	211.50	D006194	1.50	0.212		0.212
	211.50	213.00	D006195	1.50	0.543		0.543
	213.00	214.50	D006196	1.50	0.399		0.399
	214.50	216.00	D006198	1.50	0.408		0.408
	216.00	217.50	D006199	1.50	0.067		0.067
	217.50	219.00	D006200	1.50	0.008		0.008
	219.00	220.50	D006201	1.50	0.010		0.010
	220.50	222.00	D006203	1.50	<0.005		0.001
	222.00	223.50	D006204	1.50	<0.005		0.001
	223.50	225.00	D006205	1.50	<0.005		0.001
	225.00	226.50	D006206	1.50	<0.005		0.001
	226.50	228.00	D006208	1.50	0.010		0.010
	228.00	229.50	D006209	1.50	<0.005		0.001
	229.50	231.00	D006210	1.50	<0.005		0.001
	231.00	232.50	D006211	1.50	<0.005		0.001
	232.50	234.00	D006212	1.50	<0.005		0.001
	234.00	235.50	D006213	1.50	0.999		0.999
	235.50	237.00	D006214	1.50	0.339		0.339
	237.00	238.50	D006215	1.50	0.006		0.006
	238.50	240.00	D006216	1.50	<0.005		0.001
	240.00	241.50	D006218	1.50	<0.005		0.001
	241.50	243.00	D006219	1.50	<0.005		0.001
	243.00	244.50	D006220	1.50	0.031		0.031
	244.50	246.00	D006221	1.50	0.010		0.010
	246.00	247.50	D006222	1.50	0.012		0.012



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	247.50	249.00	D006223	1.50	0.028		0.028
	249.00	250.50	D006224	1.50	0.005		0.005
	250.50	252.00	D006225	1.50	<0.005		0.001
	252.00	253.50	D006226	1.50	<0.005		0.001
	253.50	255.00	D006228	1.50	<0.005		0.001
	255.00	256.50	D006229	1.50	<0.005		0.001
	256.50	258.00	D006230	1.50	<0.005		0.001
	258.00	259.50	D006231	1.50	<0.005		0.001
	259.50	261.00	D006232	1.50	0.087		0.087
	261.00	262.50	D006233	1.50	0.022		0.022
	262.50	264.00	D006234	1.50	0.012		0.012
	264.00	265.50	D006235	1.50	0.034		0.034
	265.50	267.00	D006236	1.50	<0.005		0.001
	267.00	268.50	D006238	1.50	<0.005		0.001
	268.50	270.00	D006239	1.50	<0.005		0.001
	270.00	271.50	D006240	1.50	<0.005		0.001
	271.50	273.00	D006241	1.50	<0.005		0.001
	273.00	274.50	D006243	1.50	<0.005		0.001
	274.50	276.00	D006244	1.50	<0.005		0.001
	276.00	277.50	D006245	1.50	<0.005		0.001
	277.50	279.00	D006246	1.50	<0.005		0.001
	279.00	280.50	D006248	1.50	0.035		0.035
	280.50	282.00	D006249	1.50	0.008		0.008
	282.00	283.50	D006250	1.50	0.019		0.019
	283.50	285.00	D006251	1.50	<0.005		0.001
	285.00	286.50	D006252	1.50	<0.005		0.001
	286.50	288.00	D006253	1.50	<0.005		0.001
	288.00	289.50	D006254	1.50	<0.005		0.001
	289.50	291.00	D006255	1.50	<0.005		0.001
	291.00	292.50	D006256	1.50	<0.005		0.001
	292.50	294.00	D006258	1.50	<0.005		0.001
	294.00	295.50	D006259	1.50	<0.005		0.001
	295.50	297.00	D006260	1.50	0.179		0.179

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	297.00	298.50	D006261	1.50	0.008		0.008
	298.50	300.00	D006262	1.50	<0.005		0.001
	300.00	301.50	D006263	1.50	<0.005		0.001
	301.50	303.00	D006264	1.50	<0.005		0.001
	303.00	304.50	D006265	1.50	0.020		0.020
	304.50	306.00	D006266	1.50	0.007		0.007
	306.00	307.50	D006268	1.50	0.006		0.006
	307.50	309.00	D006269	1.50	0.011		0.011
	309.00	310.50	D006270	1.50	0.008		0.008
	310.50	312.00	D006271	1.50	0.041		0.041
	312.00	313.50	D006272	1.50	0.083		0.083
	313.50	315.00	D006273	1.50	0.010		0.010
	315.00	316.50	D006274	1.50	0.007		0.007
	316.50	318.00	D006275	1.50	0.024		0.024
	318.00	319.50	D006276	1.50	0.018		0.018
	319.50	321.00	D006278	1.50	0.013		0.013
	321.00	322.50	D006279	1.50	0.010		0.010
	322.50	324.00	D006280	1.50	<0.005		0.001
	324.00	325.50	D006281	1.50	<0.005		0.001
	325.50	327.00	D006283	1.50	0.009		0.009
	327.00	328.50	D006284	1.50	0.024		0.024
	328.50	330.00	D006285	1.50	<0.005		0.001
	330.00	331.50	D006286	1.50	0.025		0.025
	331.50	333.00	D006288	1.50	0.008		0.008
	333.00	334.50	D006289	1.50	0.011		0.011
	334.50	336.00	D006290	1.50	0.069		0.069
	336.00	337.50	D006291	1.50	0.064		0.064
	337.50	339.00	D006292	1.50	0.026		0.026
	339.00	340.50	D006293	1.50	0.151		0.151
	340.50	342.00	D006294	1.50	0.008		0.008
	342.00	343.00	D006295	1.00	0.036		0.036
	343.00	344.50	D006296	1.50	0.015		0.015
	344.50	346.00	D006298	1.50	0.015		0.015

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
353.50	434.10	SY; POR <b>Syénite 35°; Porphyrique</b> Syénite porphyrique à phénocristaux à tendance Xmm à rarement Xcm et à quantité variable. Qlq veines et veinules de CB reparti irrégulièrement et qlq rare VQZ. Passage MG++. Tendance rouge.	346.00	347.50	D006299	1.50	0.028		0.028
			347.50	349.00	D006300	1.50	0.008		0.008
			349.00	350.50	D006301	1.50	0.014		0.014
			350.50	352.00	D006302	1.50	<0.005		0.001
			352.00	353.50	D006303	1.50	<0.005		0.001
			353.50	355.00	D006304	1.50	<0.005		0.001
			355.00	356.50	D006305	1.50	<0.005		0.001
			356.50	358.00	D006306	1.50	0.017		0.017
			358.00	359.50	D006308	1.50	0.008		0.008
			359.50	361.00	D006309	1.50	0.046		0.046
			361.00	362.50	D006310	1.50	0.094		0.094
			362.50	364.00	D006311	1.50	0.008		0.008
			364.00	365.50	D006312	1.50	0.083		0.083
			365.50	367.00	D006313	1.50	0.039		0.039
			367.00	368.50	D006314	1.50	0.011		0.011
			368.50	370.00	D006315	1.50	0.019		0.019
			370.00	371.50	D006316	1.50	0.366		0.366
			371.50	373.00	D006318	1.50	0.009		0.009
			373.00	374.50	D006319	1.50	0.005		0.005
			374.50	376.00	D006320	1.50	<0.005		0.001
			376.00	377.50	D006321	1.50	<0.005		0.001
			377.50	379.00	D006323	1.50	0.010		0.010
			379.00	380.50	D006324	1.50	0.048		0.048
			380.50	382.00	D006325	1.50	<0.005		0.001
			382.00	383.50	D006326	1.50	<0.005		0.001
			383.50	385.00	D006328	1.50	0.006		0.006
			385.00	386.50	D006329	1.50	0.019		0.019
			386.50	388.00	D006330	1.50	<0.005		0.001
			388.00	389.50	D006331	1.50	<0.005		0.001
			389.50	391.00	D006332	1.50	0.035		0.035
			391.00	392.50	D006333	1.50	<0.005		0.001
			392.50	394.00	D006334	1.50	0.006		0.006
			394.00	395.50	D006335	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
409.28	409.60	FAI <b>Faille 35°</b> Boue de faille, épaisseur ± 4 cm.	395.50	397.00	D006336	1.50	0.025		0.025
			397.00	398.50	D006338	1.50	0.005		0.005
			398.50	400.00	D006339	1.50	0.031		0.031
			400.00	401.50	D006340	1.50	<0.005		0.001
			401.50	402.50	D006341	1.00	<0.005		0.001
			402.50	404.00	D006342	1.50	0.021		0.021
			404.00	405.50	D006343	1.50	0.015		0.015
			405.50	407.00	D006344	1.50	0.021		0.021
			407.00	408.50	D006345	1.50	0.006		0.006
			408.50	410.00	D006346	1.50	0.012		0.012
			410.00	411.50	D006348	1.50	0.007		0.007
			411.50	413.00	D006349	1.50	0.010		0.010
			413.00	414.50	D006350	1.50	<0.005		0.001
			414.50	416.00	D006351	1.50	0.021		0.021
			416.00	417.50	D006352	1.50	0.232		0.232
			417.50	419.00	D006353	1.50	2.120		2.120
			419.00	420.50	D006354	1.50	0.997		0.997
			420.50	422.00	D006355	1.50	1.300		1.300
			422.00	423.50	D006356	1.50	0.710		0.710
			423.50	425.00	D006358	1.50	1.130		1.130
425.00	426.50	D006359	1.50	1.015		1.015			
426.50	428.00	D006360	1.50	0.233		0.233			
428.00	429.50	D006361	1.50	0.249		0.249			
429.50	431.00	D006363	1.50	0.147		0.147			
431.00	432.50	D006364	1.50	0.204		0.204			
432.50	434.10	D006365	1.60	2.340		2.340			
434.10	445.70	BA; MAS; AMY; MTY; COU <b>Basalte 55°; Roche massive; Amygdalaire; Grains moyens;</b> <b>Coussiné</b> Basalte massive avec passage amygdaire, à grains fins à moyens et coussiné. VCB et qlq rare VQZ.	434.10	435.50	D006366	1.40	0.006		0.006
			435.50	437.00	D006368	1.50	0.005		0.005
			437.00	438.50	D006369	1.50	<0.005		0.001
			438.50	440.00	D006370	1.50	<0.005		0.001
			440.00	441.50	D006371	1.50	<0.005		0.001
			441.50	443.00	D006372	1.50	0.005		0.005
			443.00	444.50	D006373	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
445.70	455.50	TU; FIN; MTY <b>Tuf à cendre/lapillis 45°; Grains fins; Grains moyens</b> Tuf à cendre/lapillis à grains à grains moyens, inclusion de qlq fragments Xcm de CB et QZ, faiblement cisailé.	444.50	445.70	D006374	1.20	<0.005		0.001
			445.70	447.00	D006375	1.30	<0.005		0.001
			447.00	448.50	D006376	1.50	<0.005		0.001
			448.50	450.00	D006378	1.50	<0.005		0.001
			450.00	451.00	D006379	1.00	<0.005		0.001
			451.00	452.50	D006380	1.50	<0.005		0.001
			452.50	454.00	D006381	1.50	<0.005		0.001
			454.00	455.50	D006382	1.50	<0.005		0.001
455.50	491.00	BA; AMY; APH; FIN <b>Basalte 55°; Amygdalaire; Aphanitique; Grains fins</b> Basalte massive avec passage amygdalaire, à aphanitique à grains fins et coussiné. VCB et qlq rare VQZ.	455.50	457.00	D006383	1.50	<0.005		0.001
			457.00	458.50	D006384	1.50	<0.005		0.001
			458.50	460.00	D006385	1.50	<0.005		0.001
			460.00	461.50	D006386	1.50	<0.005		0.001
			461.50	463.00	D006388	1.50	<0.005		0.001
			463.00	464.50	D006389	1.50	<0.005		0.001
			464.50	466.00	D006390	1.50	<0.005		0.001
			466.00	467.00	D006391	1.00	<0.005		0.001
			467.00	468.50	D006392	1.50	<0.005		0.001
			468.50	470.00	D006393	1.50	<0.005		0.001
			470.00	471.50	D006394	1.50	<0.005		0.001
			471.50	473.00	D006395	1.50	<0.005		0.001
			473.00	474.50	D006396	1.50	<0.005		0.001
			474.50	476.00	D006398	1.50	<0.005		0.001
			476.00	477.50	D006399	1.50	<0.005		0.001
			477.50	479.00	D006400	1.50	<0.005		0.001
			479.00	480.50	D006401	1.50	<0.005		0.001
480.50	482.00	D006403	1.50	<0.005		0.001			
482.00	483.50	D006404	1.50	<0.005		0.001			
483.50	485.00	D006405	1.50	<0.005		0.001			
485.00	486.50	D006406	1.50	<0.005		0.001			
486.50	488.00	D006408	1.50	<0.005		0.001			
488.00	489.50	D006409	1.50	0.005		0.005			
489.50	491.00	D006410	1.50	<0.005		0.001			

491.00

Fin du sondage

Nombre d'échantillons : 328

Nombre d'échantillons QAQC : 48

Longueur totale échantillonnée : 488.50

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.00	5.50	D006037	D006036	1.50	<0.005	0.001
10.00	11.50	D006042	M1	1.50	<0.005	0.001
16.00	17.50	D006047	D2	1.50	0.848	0.848
29.50	31.00	D006057	D006056	1.50	0.023	0.023
43.00	44.50	D006067	B4	1.50	2.590	2.590
56.50	58.00	D006077	D006076	1.50	0.009	0.009
62.50	64.00	D006082	M1	1.50	<0.005	0.001
68.50	70.00	D006087	F2	1.50	8.110	8.110
82.00	83.50	D006097	D006096	1.50	<0.005	0.001
95.50	97.00	D006107	H	1.50	0.972	0.972
109.00	110.50	D006117	D006116	1.50	<0.005	0.001
115.00	116.50	D006122	M1	1.50	<0.005	0.001
121.00	122.50	D006127	D2	1.50	0.866	0.866
134.50	136.00	D006137	D006136	1.50	<0.005	0.001
147.00	148.50	D006147	A3	1.50	0.590	0.590
160.50	162.00	D006157	D006156	1.50	<0.005	0.001
166.50	168.00	D006162	M1	1.50	<0.005	0.001
172.50	174.00	D006167	G2	1.50	4.020	4.020
186.00	187.50	D006177	D006176	1.50	<0.005	0.001
199.50	201.00	D006187	C4	1.50	1.375	1.375
213.00	214.50	D006197	D006196	1.50	0.392	0.392
219.00	220.50	D006202	M1	1.50	<0.005	0.001
225.00	226.50	D006207	D2	1.50	0.887	0.887
238.50	240.00	D006217	D006216	1.50	<0.005	0.001
252.00	253.50	D006227	F2	1.50	8.510	8.510
265.50	267.00	D006237	D006236	1.50	<0.005	0.001
271.50	273.00	D006242	M1	1.50	<0.005	0.001
277.50	279.00	D006247	G2	1.50	4.060	4.060
291.00	292.50	D006257	D006256	1.50	0.009	0.009
304.50	306.00	D006267	H	1.50	1.015	1.015
318.00	319.50	D006277	D006276	1.50	0.019	0.019
324.00	325.50	D006282	M1	1.50	<0.005	0.001
330.00	331.50	D006287	A3	1.50	0.609	0.609

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
343.00	344.50	D006297	D006296	1.50	0.020	0.020
356.50	358.00	D006307	B4	1.50	2.690	2.690
370.00	371.50	D006317	D006316	1.50	0.013	0.013
376.00	377.50	D006322	M1	1.50	<0.005	0.001
383.50	385.00	D006327	C4	1.50	1.345	1.345
395.50	397.00	D006337	D006336	1.50	0.016	0.016
408.50	410.00	D006347	D2	1.50	0.860	0.860
422.00	423.50	D006357	D006356	1.50	0.791	0.791
428.00	429.50	D006362	M1	1.50	<0.005	0.001
434.10	435.50	D006367	F2	1.40	8.780	8.470
447.00	448.50	D006377	D006376	1.50	<0.005	0.001
460.00	461.50	D006387	G2	1.50	4.190	4.060
473.00	474.50	D006397	D006396	1.50	<0.005	0.001
479.00	480.50	D006402	M1	1.50	<0.005	0.001
485.00	486.50	D006407	H	1.50	0.935	0.935



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-145**

Titre minier :

Section :

Canton :

Niveau :

Rang :

Place de travail :

Foré par :      Bradley

Lot :

Décrit par :      Gilles. KAMTA

Du :              2010-03-21

Date de description :

Au :              2010-03-23

Collet

UTM

Azimut :            0.00°  
 Plongée :          -60.00°  
 Longueur :        163.60 m

Est	630 000.0
Nord	5 374 299.9
Élévation	282.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	350.60°	-59.00°	Oui
Reflex	5.00	350.60°	-59.00°	Oui
Reflex	8.00	345.30°	-59.00°	Oui
Reflex	11.00	0.20°	-59.10°	Non
Reflex	14.00	0.10°	-59.00°	Non
Reflex	17.00	359.70°	-59.10°	Non
Reflex	20.00	359.80°	-59.10°	Non
Reflex	23.00	358.40°	-59.00°	Non
Reflex	26.00	357.90°	-59.10°	Non
Reflex	29.00	358.80°	-59.10°	Non
Reflex	32.00	0.20°	-59.10°	Oui
Reflex	35.00	359.00°	-59.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.90°	-59.10°	Non
Reflex	41.00	359.30°	-59.10°	Non
Reflex	44.00	0.40°	-59.20°	Non
Reflex	47.00	0.10°	-59.20°	Non
Reflex	50.00	359.50°	-59.10°	Non
Reflex	53.00	0.20°	-59.20°	Non
Reflex	56.00	359.80°	-59.20°	Non
Reflex	59.00	0.20°	-59.20°	Non
Reflex	62.00	359.30°	-59.30°	Non
Reflex	65.00	359.60°	-59.20°	Non
Reflex	68.00	0.50°	-59.30°	Non
Reflex	71.00	359.70°	-59.20°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.40°	-59.20°	Non					
Reflex	77.00	0.50°	-59.30°	Non					
Reflex	80.00	358.90°	-59.30°	Non					
Reflex	83.00	0.50°	-59.30°	Non					
Reflex	86.00	359.60°	-59.30°	Non					
Reflex	89.00	0.20°	-59.30°	Non					
Reflex	92.00	0.20°	-59.30°	Non					
Reflex	95.00	360.00°	-59.30°	Non					
Reflex	98.00	358.70°	-59.30°	Oui					
Reflex	101.00	359.40°	-59.30°	Non					
Reflex	104.00	359.40°	-59.30°	Non					
Reflex	107.00	0.60°	-59.30°	Non					
Reflex	110.00	359.70°	-59.30°	Non					
Reflex	113.00	1.30°	-59.20°	Non					
Reflex	116.00	0.50°	-59.30°	Oui					
Reflex	119.00	1.30°	-59.30°	Non					
Reflex	122.00	2.30°	-59.20°	Non					
Reflex	125.00	1.10°	-59.20°	Non					
Reflex	128.00	0.20°	-59.20°	Non					
Reflex	131.00	2.50°	-59.20°	Oui					
Reflex	134.00	1.20°	-59.30°	Non					
Reflex	137.00	1.20°	-59.30°	Non					
Reflex	140.00	3.00°	-59.30°	Non					
Reflex	143.00	0.50°	-59.30°	Non					
Reflex	146.00	359.60°	-59.30°	Non					
Reflex	149.00	359.00°	-59.30°	Non					
Reflex	152.00	359.90°	-59.40°	Non					
Reflex	155.00	0.80°	-59.40°	Non					
Reflex	158.00	0.40°	-59.30°	Non					
Reflex	161.00	0.60°	-59.40°	Non					
Reflex	163.60	0.80°	-59.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	10.00	MT						
		<b>Mort-terrain</b>						
10.00	163.60	SY; MAS; POR; MAG; FIN; MTY	10.00	11.50	D001282	1.50	0.015	0.015
		<b>Syénite; Roche massive; Porphyrique; Magnétique; Grains fins; Grains moyens</b>	11.50	13.00	D001283	1.50	0.277	0.277
		massive induré, avec qlq phénocristaux de FP automorphe 0.2-0.6 mm, altération potassive, localement calcite, oxydes de carbonâtes, CL+, SR+	13.00	14.50	D001284	1.50	0.042	0.042
			14.50	16.00	D001285	1.50	0.039	0.039
			16.00	17.50	D001286	1.50	0.431	0.431
			17.50	19.00	D001287	1.50	0.063	0.063
			19.00	20.50	D001288	1.50	0.009	0.009
			20.50	22.00	D001289	1.50	<0.005	0.001
			22.00	23.50	D001290	1.50	0.012	0.012
			23.50	25.00	D001292	1.50	0.013	0.013
			25.00	26.50	D001293	1.50	0.022	0.022
			26.50	28.00	D001294	1.50	0.023	0.023
			28.00	29.50	D001295	1.50	0.010	0.010
			29.50	31.00	D001296	1.50	0.082	0.082
			31.00	32.50	D001297	1.50	0.018	0.018
			32.50	34.00	D001298	1.50	0.051	0.051
			34.00	35.50	D001299	1.50	0.081	0.081
			35.50	37.00	D001300	1.50	0.008	0.008
			37.00	38.50	D001302	1.50	0.065	0.065
			38.50	40.00	D001303	1.50	0.012	0.012
			40.00	41.50	D001304	1.50	0.045	0.045
			41.50	43.00	D001305	1.50	0.036	0.036
			43.00	44.50	D001306	1.50	0.580	0.580
			44.50	46.00	D001307	1.50	0.553	0.553
			46.00	47.50	D001308	1.50	0.804	0.804
			47.50	49.00	D001309	1.50	0.029	0.029
			49.00	50.50	D001310	1.50	<0.005	0.001
			50.50	52.00	D001312	1.50	0.045	0.045
			52.00	53.50	D001313	1.50	0.020	0.020
			53.50	55.00	D001314	1.50	0.010	0.010
			55.00	56.50	D001315	1.50	0.013	0.013
			56.50	58.00	D001316	1.50	0.011	0.011

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			58.00	59.50	D001317	1.50		0.032		0.032
			59.50	61.00	D001318	1.50		0.019		0.019
			61.00	62.50	D001319	1.50		<0.005		0.001
			62.50	64.00	D001320	1.50		<0.005		0.001
			64.00	65.50	D001322	1.50		<0.005		0.001
			65.50	67.00	D001323	1.50		0.025		0.025
			67.00	68.50	D001324	1.50		0.017		0.017
			68.50	70.00	D001325	1.50		0.077		0.077
			70.00	71.50	D001326	1.50		0.206		0.206
			71.50	72.50	D001327	1.00		0.058		0.058
72.50	73.50	SY; MOY	72.50	73.50	D001328	1.00		0.273		0.273
		<b>Syénite; Grains moyens</b>	73.50	75.00	D001329	1.50		0.650		0.650
		massive, légèrement cisailé, altération K+++, oxyde de	75.00	76.50	D001330	1.50		0.121		0.121
		carbonates, SR+	76.50	78.00	D001332	1.50		0.160		0.160
			78.00	79.50	D001333	1.50		0.235		0.235
			79.50	81.00	D001334	1.50		0.087		0.087
			81.00	82.50	D001335	1.50		0.209		0.209
			82.50	84.00	D001336	1.50		<0.005		0.001
			84.00	85.50	D001337	1.50		0.077		0.077
			85.50	87.00	D001338	1.50		0.021		0.021
			87.00	88.50	D001339	1.50		<0.005		0.001
			88.50	90.00	D001340	1.50		<0.005		0.001
			90.00	91.50	D001342	1.50		<0.005		0.001
			91.50	93.00	D001343	1.50		<0.005		0.001
			93.00	94.50	D001344	1.50		<0.005		0.001
			94.50	96.00	D001345	1.50		<0.005		0.001
			96.00	97.50	D001346	1.50		<0.005		0.001
			97.50	99.00	D001347	1.50		<0.005		0.001
			99.00	100.50	D001348	1.50		<0.005		0.001
			100.50	102.00	D001349	1.50		<0.005		0.001
			102.00	103.50	D001350	1.50		<0.005		0.001
			103.50	105.00	D001352	1.50		<0.005		0.001
			105.00	106.50	D001353	1.50		0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			106.50	108.00	D001354	1.50		0.021	0.021
			108.00	109.50	D001355	1.50		0.327	0.327
			109.50	111.00	D001356	1.50		0.015	0.015
			111.00	112.50	D001357	1.50		<0.005	0.001
			112.50	114.00	D001358	1.50		<0.005	0.001
			114.00	115.50	D001359	1.50		<0.005	0.001
			115.50	117.00	D001360	1.50		<0.005	0.001
			117.00	118.50	D001362	1.50		<0.005	0.001
			118.50	120.00	D001363	1.50		<0.005	0.001
			120.00	121.50	D001364	1.50		<0.005	0.001
			121.50	123.00	D001365	1.50		<0.005	0.001
			123.00	124.50	D001366	1.50		<0.005	0.001
			124.50	126.00	D001367	1.50		0.022	0.022
			126.00	127.50	D001368	1.50		0.072	0.072
			127.50	129.00	D001369	1.50		<0.005	0.001
			129.00	130.50	D001370	1.50		<0.005	0.001
			130.50	132.00	D001372	1.50		<0.005	0.001
			132.00	133.50	D001373	1.50		<0.005	0.001
			133.50	135.00	D001374	1.50		0.078	0.078
135.00	136.50	SY; FIN	135.00	136.50	D001375	1.50		0.027	0.027
		<b>Syénite; Grains fins</b>	136.50	138.00	D001376	1.50		<0.005	0.001
		massive grains fin, altération en calcite séricite biotite, faiblement hématisé, PY fine diss	138.00	139.50	D001377	1.50		0.148	0.148
			139.50	141.00	D001378	1.50		0.812	0.812
			141.00	142.50	D001379	1.50		0.091	0.091
			142.50	144.00	D001380	1.50		<0.005	0.001
			144.00	145.50	D001382	1.50		0.028	0.028
			145.50	147.00	D001383	1.50		<0.005	0.001
			147.00	148.00	D001384	1.00		0.007	0.007
148.00	163.60	SY; MAS; FIN	148.00	149.50	D001385	1.50		<0.005	0.001
		<b>Syénite; Roche massive; Grains fins</b>	149.50	151.00	D001386	1.50		<0.005	0.001
		légèrement blanchi lessivage, altération en calcite, rares phénocristaux automorphe, localement sub bréchique et cisailé, biotite, séricite, PY fine	151.00	152.50	D001387	1.50		<0.005	0.001
			152.50	154.00	D001388	1.50		<0.005	0.001
			154.00	155.50	D001389	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	155.50	157.00	D001390	1.50	0.007		0.007
	157.00	158.50	D001392	1.50	<0.005		0.001
	158.50	160.00	D001393	1.50	<0.005		0.001
	160.00	161.50	D001394	1.50	0.007		0.007
	161.50	162.50	D001395	1.00	0.025		0.025
	162.50	163.60	D001396	1.10	0.013		0.013
<p>163.60 Fin du sondage            Nombre d'échantillons : 104            Nombre d'échantillons QAQC : 11            Longueur totale échantillonnée : 153.60</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
22.00	23.50	D001291	D001290	1.50	0.010	0.010
35.50	37.00	D001301	A3	1.50	0.591	0.591
49.00	50.50	D001311	D001310	1.50	0.006	0.006
62.50	64.00	D001321	M1	1.50	<0.005	0.001
75.00	76.50	D001331	D001330	1.50	0.142	0.142
88.50	90.00	D001341	B4	1.50	2.580	2.580
102.00	103.50	D001351	D001350	1.50	<0.005	0.001
115.50	117.00	D001361	M1	1.50	<0.005	0.001
129.00	130.50	D001371	D001370	1.50	<0.005	0.001
142.50	144.00	D001381	C4	1.50	1.415	1.415
155.50	157.00	D001391	D001390	1.50	<0.005	0.001





Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	182.00°	-60.20°	Non
Reflex	77.00	180.10°	-60.30°	Oui
Reflex	80.00	181.00°	-60.10°	Non
Reflex	83.00	181.00°	-60.10°	Non
Reflex	86.00	181.50°	-60.10°	Non
Reflex	89.00	181.80°	-60.20°	Non
Reflex	92.00	182.00°	-60.40°	Non
Reflex	95.00	182.20°	-60.20°	Non
Reflex	98.00	182.80°	-60.10°	Non
Reflex	101.00	182.00°	-60.20°	Non
Reflex	104.00	182.40°	-60.30°	Non
Reflex	107.00	182.30°	-60.10°	Non
Reflex	110.00	182.40°	-60.20°	Non
Reflex	113.00	182.20°	-60.20°	Non
Reflex	116.00	182.20°	-60.20°	Non
Reflex	119.00	182.40°	-60.30°	Non
Reflex	122.00	183.20°	-60.20°	Non
Reflex	125.00	184.60°	-60.00°	Non
Reflex	128.00	184.90°	-60.20°	Non
Reflex	131.00	184.70°	-59.90°	Non
Reflex	134.00	185.90°	-59.90°	Non
Reflex	137.00	185.70°	-59.90°	Non
Reflex	140.00	185.70°	-59.80°	Non
Reflex	143.00	185.20°	-59.70°	Non
Reflex	146.00	184.90°	-59.90°	Non
Reflex	149.00	185.10°	-59.80°	Non
Reflex	152.00	184.40°	-59.90°	Non
Reflex	155.00	183.70°	-59.80°	Non
Reflex	158.00	184.30°	-59.60°	Non
Reflex	161.00	184.30°	-59.80°	Non
Reflex	164.00	184.40°	-59.80°	Non
Reflex	167.00	184.60°	-59.70°	Non
Reflex	170.00	184.20°	-59.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	184.20°	-59.40°	Non
Reflex	176.00	185.10°	-59.20°	Non
Reflex	179.00	184.40°	-59.10°	Non
Reflex	182.00	183.80°	-58.70°	Non
Reflex	185.00	184.00°	-58.30°	Non
Reflex	188.00	185.20°	-58.10°	Non
Reflex	191.00	185.20°	-57.80°	Non
Reflex	194.00	185.10°	-57.60°	Non
Reflex	197.00	185.10°	-57.20°	Non
Reflex	200.00	185.00°	-57.00°	Non
Reflex	203.00	184.50°	-56.80°	Non
Reflex	206.00	184.60°	-56.70°	Non
Reflex	209.00	185.10°	-56.30°	Non
Reflex	212.00	185.20°	-56.10°	Non
Reflex	215.00	185.10°	-55.80°	Non
Reflex	218.00	185.20°	-55.70°	Non
Reflex	221.00	184.90°	-55.50°	Non
Reflex	224.00	185.20°	-55.20°	Non
Reflex	227.00	185.10°	-55.00°	Non
Reflex	230.00	185.30°	-55.00°	Non
Reflex	233.00	185.20°	-54.70°	Non
Reflex	236.00	185.50°	-54.30°	Non
Reflex	239.00	185.20°	-54.00°	Non
Reflex	242.00	185.40°	-53.80°	Non
Reflex	245.00	185.00°	-53.50°	Non
Reflex	248.00	185.10°	-53.20°	Non
Reflex	251.00	185.10°	-52.90°	Non
Reflex	254.00	185.40°	-52.40°	Non
Reflex	257.00	185.20°	-52.10°	Non
Reflex	260.00	185.60°	-52.00°	Non
Reflex	263.00	185.60°	-51.80°	Non
Reflex	266.00	185.90°	-51.60°	Non
Reflex	269.00	186.30°	-51.30°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	186.60°	-51.10°	Non	Reflex	371.00	183.50°	-40.10°	Non
Reflex	275.00	185.90°	-50.90°	Non					
Reflex	278.00	186.50°	-50.80°	Non					
Reflex	281.00	186.80°	-50.40°	Non					
Reflex	284.00	186.80°	-50.10°	Non					
Reflex	287.00	186.10°	-49.90°	Non					
Reflex	290.00	186.80°	-49.80°	Non					
Reflex	293.00	186.60°	-49.60°	Non					
Reflex	296.00	185.70°	-49.10°	Non					
Reflex	299.00	185.10°	-49.20°	Non					
Reflex	302.00	184.60°	-48.80°	Non					
Reflex	305.00	184.30°	-48.50°	Non					
Reflex	308.00	184.10°	-48.30°	Non					
Reflex	311.00	183.30°	-47.90°	Non					
Reflex	314.00	183.70°	-47.70°	Non					
Reflex	317.00	184.00°	-46.80°	Non					
Reflex	320.00	183.70°	-46.00°	Non					
Reflex	323.00	184.50°	-45.40°	Non					
Reflex	326.00	184.70°	-44.90°	Non					
Reflex	329.00	184.80°	-44.60°	Non					
Reflex	332.00	184.40°	-44.30°	Non					
Reflex	335.00	184.50°	-44.30°	Non					
Reflex	338.00	184.50°	-43.90°	Non					
Reflex	341.00	184.60°	-43.30°	Non					
Reflex	344.00	184.50°	-43.10°	Non					
Reflex	347.00	184.50°	-42.80°	Non					
Reflex	350.00	184.00°	-42.50°	Non					
Reflex	353.00	184.60°	-42.10°	Non					
Reflex	356.00	184.30°	-41.70°	Non					
Reflex	359.00	184.40°	-41.70°	Non					
Reflex	362.00	184.00°	-41.20°	Non					
Reflex	365.00	183.80°	-40.90°	Non					
Reflex	368.00	184.00°	-40.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	9.30	MT							
		<b>Mort-terrain</b>							
9.30	104.65	SY	9.30	11.00	D016501	1.70	0.031		0.031
		<b>Syénite 60°</b>							
		Heterogeneous; reddish gray, locally reddish green; fine-grained; cataclastic; locally porphyritic; locally brecciated; magnetic; sharp lower contact (laminations in underlying mafic tuff) @ 60 DTCA	11.00	12.50	D016502	1.50	<0.005		0.001
			12.50	14.00	D016503	1.50	0.006		0.006
			14.00	15.50	D016504	1.50	<0.005		0.001
			15.50	17.00	D016505	1.50	0.011		0.011
			17.00	18.50	D016506	1.50	<0.005		0.001
			18.50	20.00	D016507	1.50	0.108		0.108
			20.00	21.50	D016508	1.50	<0.005		0.001
			21.50	23.00	D016510	1.50	0.032		0.032
			23.00	24.50	D016511	1.50	0.005		0.005
			24.50	26.00	D016512	1.50	<0.005		0.001
			26.00	27.50	D016513	1.50	<0.005		0.001
			27.50	29.00	D016514	1.50	<0.005		0.001
			29.00	30.50	D016515	1.50	<0.005		0.001
			30.50	32.00	D016516	1.50	<0.005		0.001
			32.00	33.50	D016517	1.50	<0.005		0.001
			33.50	35.00	D016518	1.50	0.029		0.029
			35.00	36.50	D016520	1.50	0.081		0.081
			36.50	38.00	D016521	1.50	0.110		0.110
			38.00	39.00	D016522	1.00	0.009		0.009
			39.00	40.70	D016523	1.70	0.634		0.634
9.30	39.10	SY; FIN; MAS; MAG							
		<b>Syénite; Grains fins; Roche massive; Magnétique</b>							
		Heterogeneous; reddish grey and reddish green; fine-grained; scattered 0.3-1.3 cm sized euhedral Kspar phenocrysts; moderately to strongly carbonatized (Cc), moderate sericitization, weak-moderate hematitization, locally chloritized; cataclastic; scattered Cc/Qtz/Chl stringers-veinlets, essentially randomly oriented, local veinlet sets @ 45-50 DTCA, Chl generally occurs alone; local abundant discontinuous Cc/Qtz/Chl fracture fills; locally weakly brecciated, Qtz-Cc matrix; local rust-brown coloured stringers-veinlets-alteration zones, in part limonitization, but mostly probably Siderite; very fine Py disseminations in rock, rarely in later Cc/Qtz structures;							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
39.10	51.00	gradational lower contact							
		SY; BRI	40.70	42.00	D016524	1.30	4.360	4.48	4.480
		<b>Syénite; Brèche intrusive</b>	42.00	43.50	D016525	1.50	6.020	6.04	6.040
		Heterogeneous; reddish brown, reddish grey, grey, reddish green; weakly to moderately brecciated (not an intrusive breccia, no code for "breccia" in GeoticLog); Qtz (minor Cb-Cc) matrix; cross-cutting Qtz (minor Cb-Cc) stringers-veinlets; (42.85-46.0) is an essentially non-brecciated	43.50	45.00	D016526	1.50	6.510	6.69	6.690
		porphyritic-trachytic SY with ~10% 0.3-2.5 cm long euhedral Kspar phenocrysts-laths, upper contact in breccia, gradational lower contact; very fine disseminated Py in rock, rarely in Qtz/Cb/Cc structures; gradational lower contact for the whole interval	45.00	46.50	D016527	1.50	4.720	4.81	4.810
			46.50	48.00	D016528	1.50	0.328		0.328
			48.00	49.50	D016530	1.50	0.233		0.233
		49.50	51.00	D016531	1.50	1.330		1.330	
51.00	54.65	SY	51.00	52.50	D016532	1.50	0.026		0.026
		<b>Syénite</b>	52.50	54.00	D016533	1.50	0.018		0.018
		Similar to SY in (9.30-39.10)	54.00	55.50	D016534	1.50	0.115		0.115
54.65	55.25	SY; POR							
		<b>Syénite; Porphyrique</b>							
		Dykelet; pale- medium greenish gray; porphyritic - 5-15% euhedral 0.5-2.5 cm long Kspar laths, may be completely replaced by Chl; mm scale colour banding and general parallel alignment of phenocrysts @ 60-70 DTCA; minor sericitization-carbonatization-chloritization; weakly magnetic; sharp upper contact @ 55 DTCA, sharp lower contact @ 75 DTCA							
55.25	101.30	SY	55.50	57.00	D016535	1.50	0.048		0.048
		<b>Syénite</b>	57.00	58.50	D016536	1.50	0.014		0.014
		Continuation of (51.0-54.65)	58.50	60.00	D016537	1.50	0.016		0.016
			60.00	61.50	D016538	1.50	0.702		0.702
			61.50	63.00	D016540	1.50	5.770	6.24	6.240
62.55	62.75	CIS	63.00	64.50	D016541	1.50	0.009		0.009
		<b>Cisaillement 70°</b>	64.50	66.00	D016542	1.50	0.012		0.012
		Pale to medium grey and pale green; very fine-grained massive Qtz, cataclastic SY and strongly sericitized sheared-mylonitic SY layers; locally abundant fine Py along foliation (0.5% Py overall for the interval), Qtz is barren; sharp slightly irregular upper contact @ 55 DTCA, foliation and sharp lower contact @ 70 DTCA	66.00	67.50	D016543	1.50	0.489		0.489

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
66.25	67.15	CIS <b>Cisaillement 65°</b> Pale- medium green; moderate sericitization; minor-moderate carbonatization (Cc); well foliated - mylonitic, foliation @ 65 DTCA; 0.2-0.5% Py mostly along foliation planes; sharp upper contact @ 65 DTCA, gradational lower contact over 30 cm	67.50	69.00	D016544	1.50	<0.005		0.001
			69.00	70.50	D016545	1.50	<0.005		0.001
			70.50	72.00	D016546	1.50	0.007		0.007
			72.00	73.50	D016547	1.50	0.019		0.019
			73.50	75.00	D016548	1.50	<0.005		0.001
			75.00	76.50	D016550	1.50	<0.005		0.001
			76.50	78.00	D016551	1.50	0.037		0.037
76.70	77.20	CIS <b>Cisaillement 60°</b> Medium greenish red to medium green shear zone; gradational contacts over 10-20 cm; best developed foliation over 25 cm @ 60 DTCA; two 3-4 cm wide massive Qtz veins/layers with trace Py in shear zone as well; carbonatized and sericitized; 0.5-1% disseminated euhedral Py also over 25 cm in zone of best developed foliation	78.00	79.50	D016552	1.50	0.129		0.129
			79.50	81.00	D016553	1.50	0.008		0.008
			81.00	82.70	D016554	1.70	0.095		0.095
			82.70	84.00	D016555	1.30	0.011		0.011
			84.00	85.50	D016556	1.50	0.038		0.038
			85.50	87.00	D016557	1.50	0.228		0.228
			87.00	88.50	D016558	1.50	0.073		0.073
			88.50	90.00	D016560	1.50	0.028		0.028
			90.00	91.20	D016561	1.20	0.055		0.055
			91.20	92.90	D016562	1.70	0.077		0.077
			92.90	94.50	D016563	1.60	0.031		0.031
			94.50	96.00	D016564	1.50	<0.005		0.001
			96.00	97.50	D016565	1.50	<0.005		0.001
			97.50	99.00	D016566	1.50	<0.005		0.001
99.00	100.50	D016567	1.50	0.005		0.005			
100.50	102.00	D016568	1.50	0.034		0.034			
101.30	104.65	SY <b>Syénite</b> Contact zone SY; moderately fractured; carbonatized; sericitized; chloritized							
101.30	104.65	FRC <b>Fracturé</b> Contact zone SY; moderately fractured; carbonatized; sericitized; chloritized; abundant Cc/Qtz/Chl veins-flooding	102.00	103.50	D016570	1.50	0.180		0.180
			103.50	104.65	D016571	1.15	0.170		0.170
104.65	105.35	TU; LAM; MAG <b>Tuf mafique 70°; Laminations parallèles; Magnétique</b> Intercalation; medium green-grey; chloritized; carbonatized; mm-cm scale laminations @ 60 DTCA; disseminated Py; slightly irregular	104.65	106.00	D016572	1.35	0.111		0.111

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
105.35	110.65	sharp lower contact @ 70 DTCA							
		MS; LAM; MAG	106.00	107.50	D016573	1.50	0.100		0.100
		<b>Mudstone 60°; Laminations parallèles; Magnétique</b>	107.50	109.00	D016574	1.50	0.565		0.565
		Mudstone - siltstone; mm-cm wide intercalations; some interdigitation; medium grey to black and medium green; rare slump features; laminations @ 80 DTCA; pervasive carbonatization; locally weakly magnetic; Py, and lesser Aspy, as disseminations, along bedding, in mm long discontinuous stringers in fractures, occasionally in Cc-Qtz veinlets-veins; Graphite-coated bedding-fracture planes; sharp very irregular lower contact @ 60 DTCA	109.00	110.65	D016575	1.65	0.086		0.086
110.65	133.05	TU	110.65	112.00	D016576	1.35	<0.005		0.001
		<b>Tuf mafique 65°</b>	112.00	113.50	D016577	1.50	0.010		0.010
		Medium green; well laminated, mostly 1-5 mm wide laminations, rarely up to 5 cm wide; laminations may be primary remnants, due to deformation (Ser-rich), and as foliation parallel Qtz/Cc stringers-veinlets; foliation-laminations vary from 55-90 DTCA, local cm-dm scale open folds; sericitized; locally carbonatized; local Graphite/Chl-coated bedding-fracture planes; mostly trace diss Py in sericitized tuff, rarely in Qtz-Cc structures; about 20% chunky Py in sample interval (125.7-127.4); lowermost 0.8 m of interval in contact zone marked by numerous parallel Cc-Qtz veinlets-veins and strongly sericitized tuff laminations @ 65 DTCA; lower contact also @ 65 DTCA placed at the first appearance of black Talc schist (ultramafic)	113.50	115.00	D016578	1.50	0.256		0.256
			115.00	116.50	D016580	1.50	0.286		0.286
			116.50	118.00	D016581	1.50	0.283		0.283
			118.00	119.50	D016582	1.50	0.272		0.272
			119.50	121.00	D016583	1.50	0.251		0.251
			121.00	122.50	D016584	1.50	0.107		0.107
			122.50	124.00	D016585	1.50	0.281		0.281
			124.00	125.70	D016586	1.70	0.181		0.181
			125.70	127.40	D016587	1.70	0.728		0.728
			127.40	129.00	D016588	1.60	0.007		0.007
		133.05	172.35	TCSH; LAM	129.00	130.50	D016590	1.50	0.007
<b>Schiste à tacl-carbonate 45°; Laminations parallèles</b>	130.50			131.50	D016591	1.00	0.011		0.011
Mostly well laminated; black mm-cm, local dm, scale Talc schist (ultramafic protolith) laminations-remnants intercalated with abundant, up to 75%, white Cc, lesser Qtz, laminations-veinlets-veins-shreds; local medium green Ser-rich laminations at beginning of interval; laminations (and foliation) generally @ 65-75 DTCA, but varies from 0 to 90 DTCA due to folding; two occurrences of cm sized spinifex textured rock; fairly sharp lower contact @ 45 DTCA	131.50			133.05	D016592	1.55	0.011		0.011
	133.05			134.50	D016593	1.45	<0.005		0.001
	134.50			136.00	D016594	1.50	<0.005		0.001
	136.00			137.50	D016595	1.50	0.005		0.005
	137.50			139.00	D016596	1.50	<0.005		0.001
	139.00			140.50	D016597	1.50	<0.005		0.001
	140.50			142.00	D016598	1.50	<0.005		0.001
	142.00			143.50	D016600	1.50	<0.005		0.001
	143.50	145.00	D016601	1.50	<0.005		0.001		
	145.00	146.50	D016602	1.50	<0.005		0.001		
	146.50	148.00	D016603	1.50	<0.005		0.001		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			148.00	149.50	D016604	1.50	<0.005		0.001
			149.50	151.00	D016605	1.50	<0.005		0.001
			151.00	152.50	D016606	1.50	<0.005		0.001
			152.50	154.00	D016607	1.50	<0.005		0.001
			154.00	155.50	D016608	1.50	<0.005		0.001
			155.50	157.00	D016610	1.50	<0.005		0.001
			157.00	158.50	D016611	1.50	<0.005		0.001
			158.50	160.00	D016612	1.50	<0.005		0.001
			160.00	161.50	D016613	1.50	<0.005		0.001
			161.50	163.00	D016614	1.50	0.031		0.031
			163.00	164.50	D016615	1.50	<0.005		0.001
			164.50	166.00	D016616	1.50	<0.005		0.001
			166.00	167.50	D016617	1.50	<0.005		0.001
			167.50	169.00	D016618	1.50	0.005		0.005
168.43	168.53	FAI	169.00	170.70	D016620	1.70	<0.005		0.001
		<b>Faille 55°</b>	170.70	172.35	D016621	1.65	<0.005		0.001
		9 cm wide, pale green, fault gouge layer; strongly carbonatized; very sharp upper contact @ 60 DTCA, very sharp lower contact @ 45 DTCA							
172.35	373.70	TU; LAM	172.35	174.00	D016622	1.65	0.013		0.013
		<b>Tuf mafique; Laminations parallèles</b>	174.00	175.50	D016623	1.50	<0.005		0.001
		Mixture of medium grey - medium green; very fine-grained to fine-grained; well foliated; mostly with 1-5 mm wide laminations; locally (dm scale) very homogeneous with only scattered <1-2 mm wide Ser-rich laminations; trace very fine Py disseminations; trace very thin, foliation parallel, semi-massive Py laminations (fracture coatings); scarce Py in foliation parallel and cross cutting Cc/Qtz stringers-veinlets-veins; weakly to moderately carbonatized; sericitized; chloritized; upper 75 cm of interval contains rare, black, thin Talc schist intercalations; scattered mm-cm sized, often lens to augen shaped, clasts of varying composition (granite, tonalite, qtz diorite, gabbro, rhyolite, qtz, jasper, chert), foliation wraps around the clasts; unit is in part of clastic sedimentary origin	175.50	177.00	D016624	1.50	0.006		0.006
			177.00	178.50	D016625	1.50	0.006		0.006
			178.50	179.50	D016626	1.00	0.007		0.007
			179.50	180.50	D016627	1.00	0.010		0.010
			180.50	182.00	D016628	1.50	0.040		0.040
			182.00	183.50	D016630	1.50	0.193		0.193
			183.50	185.00	D016631	1.50	0.019		0.019
			185.00	186.60	D016632	1.60	0.007		0.007
			186.60	188.00	D016633	1.40	0.005		0.005
			188.00	189.00	D016634	1.00	0.008		0.008
			189.00	190.00	D016635	1.00	0.008		0.008
			190.00	191.00	D016636	1.00	0.008		0.008
			191.00	192.50	D016637	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	192.50	194.00	D016638	1.50	0.006		0.006
	194.00	195.50	D016640	1.50	0.007		0.007
	195.50	197.00	D016641	1.50	0.010		0.010
	197.00	198.50	D016642	1.50	0.087		0.087
	198.50	200.00	D016643	1.50	0.010		0.010
	200.00	201.50	D016644	1.50	0.015		0.015
	201.50	203.00	D016645	1.50	0.158		0.158
	203.00	204.50	D016646	1.50	0.023		0.023
	204.50	206.00	D016647	1.50	0.040		0.040
	206.00	207.50	D016648	1.50	0.010		0.010
	207.50	209.00	D016650	1.50	0.018		0.018
	209.00	210.50	D016651	1.50	0.085		0.085
	210.50	212.00	D016652	1.50	0.045		0.045
	212.00	213.50	D016653	1.50	0.021		0.021
	213.50	215.00	D016654	1.50	0.014		0.014
	215.00	216.50	D016655	1.50	0.104		0.104
	216.50	218.00	D016656	1.50	0.062		0.062
	218.00	219.50	D016657	1.50	0.028		0.028
	219.50	221.00	D016658	1.50	0.071		0.071
	221.00	222.50	D016660	1.50	0.049		0.049
	222.50	224.00	D016661	1.50	0.017		0.017
	224.00	225.50	D016662	1.50	0.057		0.057
	225.50	227.20	D016663	1.70	0.133		0.133
	227.20	228.10	D016664	0.90	0.014		0.014
	228.10	228.90	D016665	0.80	0.014		0.014
	228.90	229.70	D016666	0.80	0.170		0.170
	229.70	231.00	D016667	1.30	0.050		0.050
	231.00	232.00	D016668	1.00	0.042		0.042
	232.00	232.90	D016670	0.90	0.006		0.006
	232.90	234.10	D016671	1.20	<0.005		0.001
	234.10	235.80	D016672	1.70	0.095		0.095
	235.80	237.50	D016673	1.70	0.051		0.051
	237.50	239.00	D016674	1.50	0.012		0.012



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
240.15	261.10	TU; FIN	239.00	240.15	D016675	1.15	0.014		0.014
		<b>Tuf mafique 65°; Grains fins</b>	240.15	241.85	D016676	1.70	0.007		0.007
		Homogeneous; medium greenish grey; very well foliated; <1-2 mm wide Ser-rich laminations; foliation-laminations @ 65 DTCA; sericitized, less chloritization; no carbonatization; trace disseminated Py, scattered <2 mm wide Py-rich laminations; cm-dm-m scale intervals of this unit occur in overlying and underlying tuff as well; yellow variety (no Chlorite) of this rock also occurs in overlying and underlying tuff; may be a clastic sediment (sandstone?)	241.85	243.50	D016677	1.65	0.006		0.006
		243.50	245.00	D016678	1.50	0.009		0.009	
		245.00	246.70	D016680	1.70	0.008		0.008	
		246.70	248.00	D016681	1.30	0.013		0.013	
		248.00	249.40	D016682	1.40	0.063		0.063	
		249.40	251.00	D016683	1.60	0.011		0.011	
		251.00	252.50	D016684	1.50	0.006		0.006	
		252.50	254.10	D016685	1.60	0.007		0.007	
		254.10	255.50	D016686	1.40	0.006		0.006	
		255.50	257.00	D016687	1.50	0.008		0.008	
		257.00	258.70	D016688	1.70	0.009		0.009	
		258.70	259.50	D016690	0.80	0.006		0.006	
		259.50	261.10	D016691	1.60	0.011		0.011	
		261.10	262.50	D016692	1.40	0.061		0.061	
		262.50	264.00	D016693	1.50	0.007		0.007	
		264.00	265.60	D016694	1.60	0.006		0.006	
		265.60	267.00	D016695	1.40	0.005		0.005	
		267.00	268.50	D016696	1.50	0.005		0.005	
		268.50	270.00	D016697	1.50	0.006		0.006	
		270.00	270.80	D016698	0.80	0.005		0.005	
		270.80	272.30	D016700	1.50	0.007		0.007	
272.30	274.00	D016701	1.70	0.034		0.034			
274.00	275.50	D016702	1.50	0.011		0.011			
275.50	277.00	D016703	1.50	0.005		0.005			
277.00	278.50	D016704	1.50	0.012		0.012			
278.50	279.90	D016705	1.40	0.008		0.008			
279.90	280.80	D016706	0.90	<0.005		0.001			
280.80	282.50	D016707	1.70	0.011		0.011			
282.50	284.00	D016708	1.50	0.006		0.006			
284.00	285.50	D016710	1.50	0.010		0.010			
285.50	287.00	D016711	1.50	0.010		0.010			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
294.25	302.75	TU; FIN <b>Tuf mafique 50°; Grains fins</b> Homogeneous; similar to (240.15-261.10); medium greenish grey; very well foliated; <1-2 mm wide Ser-rich laminations; foliation-laminations @ 50 DTCA; sericitized, chloritized; no carbonatization; trace disseminated Py, scattered <2 mm wide Py-rich laminations; may be a clastic sediment (sandstone?); sharp irregular upper contact marked by a 6 cm sized irregular Qtz-Cb vein/pod, sharp lower contact @ 50 DTCA	287.00	288.50	D016712	1.50	0.008		0.008
			288.50	289.80	D016713	1.30	0.045		0.045
			289.80	290.70	D016714	0.90	0.018		0.018
			290.70	292.00	D016715	1.30	0.082		0.082
			292.00	293.00	D016716	1.00	0.143		0.143
			293.00	294.20	D016717	1.20	0.142		0.142
			294.20	295.90	D016718	1.70	0.009		0.009
			295.90	297.50	D016720	1.60	0.009		0.009
			297.50	299.10	D016721	1.60	0.005		0.005
			299.10	300.80	D016722	1.70	0.012		0.012
			300.80	302.00	D016723	1.20	0.010		0.010
			302.00	302.80	D016724	0.80	0.006		0.006
			302.80	304.00	D016725	1.20	0.045		0.045
			304.00	305.50	D016726	1.50	0.011		0.011
307.95	319.35	TU; FIN <b>Tuf mafique 55°; Grains fins</b> Homogeneous; similar to (240.15-261.10); medium greenish grey; very well foliated; <1-2 mm wide Ser-rich laminations; foliation-laminations @ 55 DTCA; sericitized, chloritized; no carbonatization; trace disseminated Py, may be a clastic sediment (sandstone?); sharp foliation parallel upper contact @ 50 DTCA, sharp lower contact @ 70 DTCA	305.50	307.00	D016727	1.50	<0.005		0.001
			307.00	308.00	D016728	1.00	<0.005		0.001
			308.00	309.50	D016730	1.50	0.005		0.005
			309.50	311.00	D016731	1.50	0.006		0.006
			311.00	312.60	D016732	1.60	<0.005		0.001
			312.60	313.40	D016733	0.80	0.005		0.005
			313.40	315.00	D016734	1.60	0.013		0.013
			315.00	316.50	D016735	1.50	0.006		0.006
			316.50	318.00	D016736	1.50	0.007		0.007
			318.00	319.30	D016737	1.30	0.015		0.015
			319.30	321.00	D016738	1.70	0.025		0.025
			321.00	322.50	D016740	1.50	0.032		0.032
			322.50	324.00	D016741	1.50	0.113		0.113
			324.00	325.50	D016742	1.50	0.035		0.035
329.40	330.50	M8; LAM <b>Schiste 70°; Laminations parallèles</b> Laminated; 1 mm - 2 cm wide dark grey fine-grained sandstone	325.50	327.00	D016743	1.50	0.016		0.016
			327.00	328.50	D016744	1.50	0.034		0.034
			328.50	329.40	D016745	0.90	0.010		0.010
			329.40	330.50	D016746	1.10	0.132		0.132

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
330.50	332.35	laminations intercalated with <1 mm - 1 cm wide dark green to black Ser/Chl laminations; laminations @ 70 DTCA; also 1 mm - 1.5 cm wide semi-massive Py laminations, locally convoluted; local Graphite-coated lamination surfaces; 10-15% Py; mm-cm scale intercalated upper contact over 10 cm, very irregular lower contact marked by slip planes and Qtz flooding TU; FIN <b>Tuf felsique 60°; Grains fins</b> Homogeneous; medium beige; well foliated, foliation @ 60 DTCA; strongly Sericitized; mm spaced Chl-coated foliation-fracture surfaces; sharp foliation parallel lower contact @ 60 DTCA						
330.50	373.70	CIS	330.50	331.50	D016747	1.00	0.022	0.022
		<b>Cisaillement 60°</b>	331.50	332.40	D016748	0.90	0.006	0.006
		Although the whole tuff unit is in a deformation zone, this interval appears to be more highly deformed; very well foliated,	332.40	333.50	D016750	1.10	0.011	0.011
		laminated; sericitized - chloritized striped rock; mostly alternating	333.50	335.00	D016751	1.50	0.008	0.008
		<1-3 mm wide green Ser-Chl and pale grey Qtz-rich laminations;	335.00	336.50	D016752	1.50	0.007	0.007
		foliation-laminations @ 35-65 DTCA; diss Py; most late Qtz-Cb	336.50	338.00	D016753	1.50	0.010	0.010
		veinlets and veins are essentially foliation parallel and barren	338.00	339.50	D016754	1.50	0.005	0.005
			339.50	341.00	D016755	1.50	0.007	0.007
			341.00	342.50	D016756	1.50	0.008	0.008
			342.50	344.10	D016757	1.60	0.009	0.009
			344.10	345.50	D016758	1.40	0.011	0.011
			345.50	347.00	D016760	1.50	0.008	0.008
			347.00	348.50	D016761	1.50	0.008	0.008
			348.50	350.00	D016762	1.50	0.006	0.006
			350.00	351.50	D016763	1.50	<0.005	0.001
			351.50	353.00	D016764	1.50	<0.005	0.001
			353.00	354.50	D016765	1.50	<0.005	0.001
			354.50	356.00	D016766	1.50	0.007	0.007
			356.00	357.00	D016767	1.00	0.011	0.011
			357.00	358.50	D016768	1.50	<0.005	0.001
			358.50	360.00	D016770	1.50	0.015	0.015
			360.00	361.10	D016771	1.10	<0.005	0.001
			361.10	362.50	D016772	1.40	0.007	0.007
			362.50	363.70	D016773	1.20	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	363.70	365.40	D016774	1.70	<0.005		0.001
	365.40	367.00	D016775	1.60	0.011		0.011
	367.00	368.50	D016776	1.50	0.006		0.006
	368.50	370.00	D016777	1.50	0.007		0.007
	370.00	371.50	D016778	1.50	<0.005		0.001
	371.50	372.90	D016780	1.40	0.005		0.005
	372.90	373.70	D016781	0.80	<0.005		0.001
<p>373.70 Fin du sondage            Nombre d'échantillons : 253            Nombre d'échantillons QAQC : 28            Longueur totale échantillonnée : 364.40</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
20.00	21.50	D016509	D016508	1.50	<0.005	0.001
33.50	33.50	D016519	A3	0.00	0.576	0.576
46.50	48.00	D016529	D016528	1.50	0.325	0.325
60.00	60.00	D016539	M1	0.00	<0.005	0.001
73.50	75.00	D016549	D016548	1.50	<0.005	0.001
87.00	87.00	D016559	B4	0.00	2.590	2.590
100.50	102.00	D016569	D016568	1.50	0.039	0.039
113.50	113.50	D016579	M1	0.00	<0.005	0.001
127.40	129.00	D016589	D016588	1.60	<0.005	0.001
140.50	140.50	D016599	C4	0.00	1.435	1.435
154.00	155.50	D016609	D016608	1.50	<0.005	0.001
167.50	167.50	D016619	M1	0.00	<0.005	0.001
180.50	182.00	D016629	D016628	1.50	0.022	0.022
192.50	192.50	D016639	D2	0.00	0.851	0.851
206.00	207.50	D016649	D016648	1.50	0.009	0.009
219.50	219.50	D016659	M1	0.00	<0.005	0.001
231.00	232.00	D016669	D016668	1.00	0.080	0.080
243.50	243.50	D016679	F2	0.00	8.230	8.570
257.00	258.70	D016689	D016688	1.70	0.008	0.008
270.00	270.00	D016699	M1	0.00	<0.005	0.001
282.50	284.00	D016709	D016708	1.50	0.007	0.007
294.20	294.20	D016719	G2	0.00	4.070	4.010
307.00	308.00	D016729	D016728	1.00	<0.005	0.001
319.30	319.30	D016739	M1	0.00	<0.005	0.001
331.50	332.40	D016749	D016748	0.90	0.007	0.007
344.10	344.10	D016759	H	0.00	0.990	0.990
357.00	358.50	D016769	D016768	1.50	0.006	0.006
370.00	370.00	D016779	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-147</b>	Titre minier :	Section :	630 000
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Guy gbaguidi	Du : 2010-03-28	Date de description :	
	Au : 2010-04-01		

Collet

Azimut : 180.00°  
 Plongée : -70.00°  
 Longueur : 308.00 m

UTM

Est	629 999.9
Nord	5 374 299.0
Élévation	282.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	44.10°	-75.70°	Oui
Reflex	5.00	314.00°	-69.60°	Oui
Reflex	8.00	314.00°	-69.70°	Oui
Reflex	11.00	164.50°	-69.60°	Oui
Reflex	14.00	168.20°	-69.60°	Oui
Reflex	17.00	182.40°	-69.80°	Non
Reflex	20.00	180.00°	-69.70°	Non
Reflex	23.00	180.00°	-69.70°	Non
Reflex	26.00	179.50°	-69.60°	Non
Reflex	29.00	179.60°	-69.50°	Non
Reflex	32.00	178.10°	-69.40°	Non
Reflex	35.00	180.50°	-69.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	178.50°	-69.30°	Non
Reflex	41.00	179.70°	-69.20°	Non
Reflex	44.00	179.70°	-69.10°	Non
Reflex	47.00	180.00°	-69.00°	Non
Reflex	50.00	179.10°	-68.90°	Non
Reflex	53.00	180.70°	-68.80°	Non
Reflex	56.00	180.60°	-68.80°	Non
Reflex	59.00	181.10°	-68.70°	Non
Reflex	62.00	182.20°	-68.70°	Non
Reflex	65.00	181.20°	-68.20°	Non
Reflex	68.00	181.20°	-68.50°	Non
Reflex	71.00	182.10°	-68.40°	Non

Description

Entre les blocs 290 et 29, seulement 3 m de carotte

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	182.00°	-68.40°	Non
Reflex	77.00	182.50°	-68.20°	Non
Reflex	80.00	183.10°	-68.00°	Non
Reflex	83.00	182.30°	-67.80°	Non
Reflex	86.00	182.00°	-67.70°	Non
Reflex	89.00	182.00°	-67.60°	Non
Reflex	92.00	182.40°	-67.60°	Non
Reflex	95.00	179.40°	-67.60°	Oui
Reflex	98.00	181.00°	-67.60°	Non
Reflex	101.00	182.60°	-67.50°	Non
Reflex	104.00	182.90°	-67.60°	Non
Reflex	107.00	185.00°	-67.50°	Non
Reflex	110.00	185.00°	-67.50°	Non
Reflex	113.00	185.10°	-67.40°	Non
Reflex	116.00	185.10°	-67.50°	Non
Reflex	119.00	185.20°	-67.20°	Non
Reflex	122.00	185.60°	-67.10°	Non
Reflex	125.00	185.30°	-67.00°	Non
Reflex	128.00	185.70°	-66.70°	Non
Reflex	131.00	185.70°	-66.50°	Non
Reflex	134.00	185.80°	-66.30°	Non
Reflex	137.00	185.80°	-66.10°	Non
Reflex	140.00	186.20°	-65.90°	Non
Reflex	143.00	186.30°	-65.70°	Non
Reflex	146.00	186.70°	-65.50°	Non
Reflex	149.00	187.20°	-65.20°	Non
Reflex	152.00	187.80°	-64.90°	Non
Reflex	155.00	187.80°	-64.60°	Non
Reflex	158.00	188.30°	-64.30°	Non
Reflex	161.00	188.50°	-64.20°	Non
Reflex	164.00	188.50°	-64.10°	Non
Reflex	167.00	188.60°	-64.00°	Non
Reflex	170.00	188.70°	-63.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	188.80°	-63.70°	Non
Reflex	176.00	189.00°	-63.70°	Non
Reflex	179.00	188.60°	-63.60°	Non
Reflex	182.00	188.40°	-63.40°	Non
Reflex	185.00	188.00°	-63.30°	Non
Reflex	188.00	188.00°	-63.10°	Non
Reflex	191.00	188.00°	-63.10°	Non
Reflex	194.00	187.90°	-63.30°	Non
Reflex	197.00	187.80°	-63.30°	Non
Reflex	200.00	187.60°	-63.20°	Non
Reflex	203.00	187.30°	-63.10°	Non
Reflex	206.00	186.80°	-63.00°	Non
Reflex	209.00	187.00°	-62.90°	Non
Reflex	212.00	186.80°	-62.80°	Non
Reflex	215.00	186.40°	-62.70°	Non
Reflex	218.00	186.50°	-62.60°	Non
Reflex	221.00	186.50°	-62.60°	Non
Reflex	224.00	186.50°	-62.60°	Non
Reflex	227.00	186.00°	-62.60°	Non
Reflex	230.00	186.00°	-62.50°	Non
Reflex	233.00	186.00°	-62.40°	Non
Reflex	236.00	186.20°	-62.30°	Non
Reflex	239.00	186.10°	-62.10°	Non
Reflex	242.00	186.10°	-61.90°	Non
Reflex	245.00	186.00°	-61.80°	Non
Reflex	248.00	186.40°	-61.60°	Non
Reflex	251.00	186.10°	-61.30°	Non
Reflex	254.00	186.10°	-61.10°	Non
Reflex	257.00	185.60°	-61.00°	Non
Reflex	260.00	185.50°	-60.70°	Non
Reflex	263.00	185.10°	-60.50°	Non
Reflex	266.00	184.80°	-60.20°	Non
Reflex	269.00	184.70°	-60.00°	Non

Corporation Minière Osisko Div. Exploration

Déviatiion

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	184.70°	-59.70°	Non					
Reflex	275.00	184.60°	-59.40°	Non					
Reflex	278.00	184.10°	-59.30°	Non					
Reflex	281.00	183.80°	-59.10°	Non					
Reflex	284.00	183.30°	-58.90°	Non					
Reflex	287.00	183.00°	-58.70°	Non					
Reflex	290.00	183.00°	-58.60°	Non					
Reflex	293.00	183.10°	-58.30°	Non					
Reflex	296.00	183.40°	-58.20°	Non					
Reflex	299.00	183.30°	-58.10°	Non					
Reflex	302.00	183.60°	-58.00°	Non					
Reflex	305.00	183.40°	-57.90°	Non					
Reflex	308.00	183.00°	-57.90°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	13.30	MT						
		<b>Mort-terrain</b>						
13.30	106.00	SY; POR	13.30	15.00	D012273	1.70	0.029	0.029
		<b>Syénite; Porphyrique</b>	15.00	16.50	D012274	1.50	0.010	0.010
		Syénite carbonatée, localement massive, localement porphyrique, cisailée par endroit.	16.50	18.00	D012276	1.50	0.010	0.010
			18.00	19.50	D012277	1.50	0.005	0.005
			19.50	21.00	D012278	1.50	0.007	0.007
			21.00	22.50	D012279	1.50	0.048	0.048
			22.50	24.00	D012281	1.50	0.035	0.035
			24.00	25.50	D012282	1.50	0.016	0.016
			25.50	27.00	D012283	1.50	0.009	0.009
			27.00	28.50	D012284	1.50	0.006	0.006
			28.50	30.00	D012286	1.50	0.006	0.006
			30.00	31.50	D012287	1.50	0.009	0.009
			31.50	33.00	D012288	1.50	0.008	0.008
			33.00	34.50	D012289	1.50	0.007	0.007
			34.50	36.00	D012290	1.50	0.010	0.010
			36.00	37.50	D012291	1.50	0.011	0.011
			37.50	39.00	D012292	1.50	0.011	0.011
			39.00	40.50	D012293	1.50	0.006	0.006
			40.50	42.00	D012294	1.50	<0.005	0.001
			42.00	43.50	D012296	1.50	0.006	0.006
			43.50	45.00	D012297	1.50	0.005	0.005
			45.00	46.50	D012298	1.50	0.017	0.017
			46.50	48.00	D012299	1.50	0.005	0.005
			48.00	49.50	D012300	1.50	0.006	0.006
			49.50	51.00	D012301	1.50	0.008	0.008
			51.00	52.30	D012302	1.30	0.042	0.042
			52.30	54.00	D012303	1.70	4.690	4.690
			54.00	55.50	D012305	1.50	>10.0	87.80
			55.50	57.00	D012307	1.50	0.692	0.692
			57.00	58.50	D012308	1.50	1.855	1.855
			58.50	60.00	D012309	1.50	2.030	2.030
			60.00	61.00	D012310	1.00	0.541	0.541

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			61.00	62.50	D012311	1.50		2.640		2.640
			62.50	64.00	D012312	1.50		0.822		0.822
			64.00	65.50	D012313	1.50		2.520		2.520
			65.50	67.00	D012314	1.50		0.680		0.680
			67.00	68.50	D012316	1.50		6.280		6.280
			68.50	70.10	D012317	1.60		8.520		8.520
			70.10	71.80	D012318	1.70		2.360		2.360
			71.80	73.00	D012319	1.20		0.889		0.889
			73.00	74.50	D012321	1.50		0.019		0.019
			74.50	76.00	D012322	1.50		0.054		0.054
			76.00	77.50	D012323	1.50		3.080		3.080
			77.50	79.00	D012324	1.50		0.117		0.117
			79.00	80.50	D012326	1.50		0.026		0.026
			80.50	82.00	D012327	1.50		0.006		0.006
			82.00	83.50	D012328	1.50		0.005		0.005
			83.50	85.00	D012329	1.50		0.018		0.018
			85.00	86.50	D012330	1.50		0.021		0.021
			86.50	88.00	D012331	1.50		0.005		0.005
			88.00	89.50	D012332	1.50		0.005		0.005
			89.50	91.00	D012333	1.50		0.006		0.006
			91.00	92.50	D012334	1.50		0.010		0.010
			92.50	94.00	D012336	1.50		0.040		0.040
			94.00	95.50	D012337	1.50		0.005		0.005
			95.50	97.00	D012338	1.50		<0.005		0.001
			97.00	98.50	D012339	1.50		0.006		0.006
			98.50	100.00	D012340	1.50		0.014		0.014
			100.00	101.50	D012341	1.50		0.148		0.148
			101.50	103.00	D012342	1.50		0.007		0.007
			103.00	104.50	D012343	1.50		0.021		0.021
			104.50	106.00	D012344	1.50		0.168		0.168
106.00	107.50	GW Grauwacke 70° Sédiments carbonatés, passablement cisailés.	106.00	107.50	D012346	1.50		0.574		0.574
107.50	109.20	SY; BR	107.50	109.20	D012347	1.70		0.136		0.136

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
109.20	110.80	<p><b>Syénite 70°; Bréchifié</b> Syénite fortement carbonatée et bréchifiée.</p> <p>GR; CIS</p>	109.20	110.80	D012348	1.60	0.206		0.206
110.80	151.00	<p><b>Grès 70°; Cisailé</b> Carbonaté avec des niveaux graphiteux, cisailé à 70-90°.</p> <p>TU; CIS</p> <p><b>Tuf à cendre/lapillis 70°; Cisailé</b> Fortement carbonaté, localement cisailé avec passages de niveaux graphiteux.</p>	110.80	112.00	D012349	1.20	0.043		0.043
			112.00	113.50	D012350	1.50	0.010		0.010
			113.50	115.00	D012351	1.50	0.006		0.006
			115.00	116.50	D012352	1.50	0.008		0.008
			116.50	118.00	D012353	1.50	0.007		0.007
			118.00	119.50	D012354	1.50	0.008		0.008
			119.50	121.00	D012356	1.50	0.012		0.012
			121.00	122.50	D012357	1.50	0.321		0.321
			122.50	124.00	D012358	1.50	0.249		0.249
			124.00	125.50	D012359	1.50	2.040		2.040
			125.50	127.00	D012360	1.50	0.408		0.408
			127.00	128.50	D012361	1.50	0.153		0.153
			128.50	130.00	D012362	1.50	0.255		0.255
			130.00	131.50	D012363	1.50	0.268		0.268
			131.50	133.00	D012364	1.50	0.340		0.340
			133.00	134.50	D012366	1.50	0.566		0.566
			134.50	136.00	D012367	1.50	0.246		0.246
			136.00	137.50	D012368	1.50	0.346		0.346
			137.50	139.00	D012369	1.50	0.255		0.255
			139.00	140.50	D012370	1.50	0.106		0.106
			140.50	142.00	D012371	1.50	0.005		0.005
			142.00	143.50	D012372	1.50	<0.005		0.001
			143.50	145.00	D012373	1.50	0.009		0.009
			145.00	146.50	D012374	1.50	0.011		0.011
			146.50	148.00	D012376	1.50	0.007		0.007
			148.00	149.50	D012377	1.50	<0.005		0.001
			149.50	151.00	D012378	1.50	0.008		0.008
151.00	232.10	<p>TCSH</p> <p><b>Schiste à tacl-carbonate 45°</b> Remplacé par endroit par injection de qtz-cc-cb.</p>	151.00	152.50	D012379	1.50	<0.005		0.001
			152.50	154.00	D012380	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	154.00	155.50	D012381	1.50	0.114		0.114
	155.50	157.00	D012382	1.50	0.006		0.006
	157.00	158.00	D012383	1.00	0.005		0.005
	158.00	159.00	D012384	1.00	<0.005		0.001
	159.00	160.50	D012386	1.50	0.005		0.005
	160.50	162.00	D012387	1.50	0.006		0.006
	162.00	163.50	D012388	1.50	<0.005		0.001
	163.50	165.00	D012389	1.50	0.006		0.006
	165.00	166.50	D012390	1.50	0.011		0.011
	166.50	168.00	D012391	1.50	0.005		0.005
	168.00	169.50	D012392	1.50	<0.005		0.001
	169.50	171.00	D012393	1.50	0.005		0.005
	171.00	172.50	D012394	1.50	<0.005		0.001
	172.50	174.00	D012396	1.50	<0.005		0.001
	174.00	175.50	D012397	1.50	<0.005		0.001
	175.50	176.50	D012398	1.00	<0.005		0.001
176.50	177.50	SY	D012399	1.00	<0.005		0.001
		<b>Syénite 79°</b>	D012401	1.50	<0.005		0.001
		Syénite silicifiée avec reliques de phénocristaux.	D012402	1.50	<0.005		0.001
			D012403	1.50	0.007		0.007
			D012404	1.50	<0.005		0.001
			D012406	1.50	<0.005		0.001
			D012407	1.50	<0.005		0.001
			D012408	1.50	<0.005		0.001
			D012409	1.50	<0.005		0.001
			D012410	1.50	<0.005		0.001
			D012411	1.50	<0.005		0.001
			D012412	1.50	0.010		0.010
			D012413	1.50	0.007		0.007
			D012414	1.50	0.014		0.014
			D012416	1.50	<0.005		0.001
			D012417	1.50	<0.005		0.001
			D012418	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			201.50	203.00	D012419	1.50	<0.005		0.001
			203.00	204.50	D012420	1.50	<0.005		0.001
			204.50	206.00	D012421	1.50	<0.005		0.001
			206.00	207.50	D012422	1.50	0.008		0.008
			207.50	209.00	D012423	1.50	0.010		0.010
			209.00	210.50	D012424	1.50	0.019		0.019
			210.50	212.00	D012426	1.50	0.017		0.017
			212.00	213.50	D012427	1.50	0.006		0.006
			213.50	215.00	D012428	1.50	0.007		0.007
			215.00	216.50	D012429	1.50	0.005		0.005
			216.50	218.00	D012430	1.50	<0.005		0.001
			218.00	219.50	D012431	1.50	0.005		0.005
			219.50	221.00	D012432	1.50	0.005		0.005
			221.00	222.50	D012433	1.50	<0.005		0.001
			222.50	224.00	D012434	1.50	<0.005		0.001
			224.00	225.50	D012436	1.50	<0.005		0.001
			225.50	227.00	D012437	1.50	<0.005		0.001
			227.00	228.50	D012438	1.50	<0.005		0.001
			228.50	230.00	D012439	1.50	<0.005		0.001
			230.00	231.00	D012441	1.00	<0.005		0.001
			231.00	232.10	D012442	1.10	<0.005		0.001
232.10	308.00	ST; MAS	232.10	233.10	D012443	1.00	<0.005		0.001
		<b>Siltstone 45°; Roche massive</b>	233.10	234.50	D012444	1.40	0.010		0.010
		Massive, localement cisailéchloritisée, séricitisée par endroit.	234.50	236.00	D012446	1.50	0.009		0.009
			236.00	237.50	D012447	1.50	0.006		0.006
			237.50	239.00	D012448	1.50	0.006		0.006
			239.00	240.50	D012449	1.50	0.007		0.007
			240.50	242.00	D012450	1.50	0.006		0.006
			242.00	243.50	D012451	1.50	0.008		0.008
			243.50	245.00	D012452	1.50	0.013		0.013
			245.00	246.50	D012453	1.50	0.026		0.026
			246.50	248.00	D012454	1.50	0.008		0.008
			248.00	249.50	D012456	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	249.50	251.00	D012457	1.50	0.006		0.006
	251.00	252.50	D012458	1.50	0.008		0.008
	252.50	254.00	D012459	1.50	0.007		0.007
	254.00	255.50	D012460	1.50	0.007		0.007
	255.50	257.00	D012461	1.50	0.007		0.007
	257.00	258.50	D012462	1.50	0.008		0.008
	258.50	260.00	D012463	1.50	0.009		0.009
	260.00	261.50	D012464	1.50	0.009		0.009
	261.50	263.00	D012466	1.50	0.007		0.007
	263.00	264.50	D012467	1.50	0.055		0.055
	264.50	266.00	D012468	1.50	0.008		0.008
	266.00	267.50	D012469	1.50	0.008		0.008
	267.50	269.00	D012470	1.50	0.013		0.013
	269.00	270.50	D012471	1.50	0.007		0.007
	270.50	272.00	D012472	1.50	0.008		0.008
	272.00	273.50	D012473	1.50	0.007		0.007
	273.50	275.00	D012474	1.50	0.006		0.006
	275.00	276.50	D012476	1.50	0.005		0.005
	276.50	278.00	D012477	1.50	0.010		0.010
	278.00	279.50	D012478	1.50	0.005		0.005
	279.50	281.00	D012479	1.50	0.019		0.019
	281.00	282.50	D012480	1.50	0.006		0.006
	282.50	284.00	D012481	1.50	0.063		0.063
	284.00	285.50	D012482	1.50	0.088		0.088
	285.50	287.00	D012483	1.50	0.108		0.108
	287.00	288.50	D012484	1.50	0.280		0.280
	288.50	290.00	D012486	1.50	0.021		0.021
	290.00	291.50	D012487	1.50	0.031		0.031
	291.50	293.00	D012488	1.50	0.028		0.028
	293.00	294.50	D012489	1.50	0.047		0.047
	294.50	296.00	D012490	1.50	0.011		0.011
	296.00	297.50	D012491	1.50	0.114		0.114
	297.50	299.00	D012492	1.50	0.024		0.024

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	299.00	300.50	D012493	1.50	0.045		0.045
	300.50	302.00	D012494	1.50	0.030		0.030
	302.00	303.50	D012496	1.50	0.009		0.009
	303.50	305.00	D012497	1.50	0.016		0.016
	305.00	306.50	D012498	1.50	0.160		0.160
	306.50	308.00	D012499	1.50	0.144		0.144
308.00	Fin du sondage Nombre d'échantillons : 199 Nombre d'échantillons QAQC : 28 Longueur totale échantillonnée : 294.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.00	16.50	D012275	B4	1.50	2.630	2.630
21.00	22.50	D012280	M1	1.50	<0.005	0.001
27.00	28.50	D012285	D012284	1.50	0.012	0.012
40.50	42.00	D012295	C4	1.50	1.345	1.345
52.30	54.00	D012304	D012303	1.70	4.750	4.750
54.00	55.50	D012306	M1	1.50	0.058	0.058
65.50	67.00	D012315	D2	1.50	0.834	0.834
71.80	73.00	D012320	M1	1.20	0.006	0.006
77.50	79.00	D012325	D012324	1.50	0.117	0.117
91.00	92.50	D012335	F2	1.50	7.710	7.710
104.50	106.00	D012345	D012344	1.50	0.225	0.225
118.00	119.50	D012355	H	1.50	0.997	0.997
131.50	133.00	D012365	D012364	1.50	0.344	0.344
145.00	146.50	D012375	A3	1.50	0.342	0.342
158.00	159.00	D012385	D012384	1.00	<0.005	0.001
171.00	171.00	D012395	B4	0.00	2.610	2.610
176.50	177.50	D012400	M1	1.00	<0.005	0.001
182.00	183.50	D012405	D012404	1.50	<0.005	0.001
195.50	195.50	D012415	C4	0.00	1.365	1.365
209.00	210.50	D012425	D012424	1.50	0.022	0.022
222.50	222.50	D012435	D2	0.00	0.831	0.831
228.50	228.50	D012440	M1	0.00	<0.005	0.001
233.10	234.50	D012445	D012444	1.40	0.011	0.011
246.50	246.50	D012455	F2	0.00	8.350	8.350
260.00	261.50	D012465	D012464	1.50	0.010	0.010
273.50	273.50	D012475	H	0.00	1.000	1.000
287.00	288.50	D012485	D012484	1.50	0.170	0.170
300.50	300.50	D012495	A3	0.00	0.578	0.578



## Corporation Minière Osisko Div. Exploration

**Sondage :**        **BD10-148**

Titre minier :

Section :            630 900

Canton :

Niveau :

Foré par :        Bradley

Rang :

Place de travail :    Malartic

Décrit par :      Guy Gbaguidi

Lot :

Du :                2010-03-29

Date de description :

Au :                2010-04-04

Collet

UTM

Azimut :            0.00°  
 Plongée :          -62.00°  
 Longueur :        452.00 m

Est	630 900.1
Nord	5 374 200.3
Élévation	300.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	357.10°	-62.80°	Oui
Reflex	5.00	348.70°	-62.60°	Oui
Reflex	8.00	359.40°	-62.40°	Oui
Reflex	11.00	349.10°	-62.40°	Oui
Reflex	14.00	348.50°	-62.40°	Oui
Reflex	17.00	357.80°	-62.20°	Oui
Reflex	20.00	353.70°	-62.80°	Oui
Reflex	23.00	166.60°	-62.60°	Oui
Reflex	26.00	0.70°	-62.10°	Non
Reflex	29.00	0.90°	-62.40°	Non
Reflex	32.00	0.30°	-62.50°	Non
Reflex	35.00	0.30°	-62.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.80°	-62.20°	Non
Reflex	41.00	359.40°	-62.20°	Non
Reflex	44.00	359.30°	-62.00°	Non
Reflex	47.00	359.60°	-61.80°	Non
Reflex	50.00	359.60°	-61.70°	Non
Reflex	53.00	359.80°	-61.60°	Non
Reflex	56.00	0.20°	-61.40°	Non
Reflex	59.00	0.40°	-61.50°	Non
Reflex	62.00	0.70°	-61.50°	Non
Reflex	65.00	1.00°	-61.60°	Non
Reflex	68.00	1.40°	-61.60°	Non
Reflex	71.00	1.80°	-61.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.10°	-61.80°	Non	Reflex	173.00	5.50°	-60.10°	Non
Reflex	77.00	2.80°	-61.70°	Non	Reflex	176.00	5.90°	-60.00°	Non
Reflex	80.00	3.60°	-61.70°	Non	Reflex	179.00	6.50°	-60.00°	Non
Reflex	83.00	4.50°	-61.70°	Non	Reflex	182.00	5.50°	-59.90°	Non
Reflex	86.00	5.50°	-61.60°	Non	Reflex	185.00	5.60°	-59.80°	Non
Reflex	89.00	6.20°	-61.50°	Non	Reflex	188.00	5.00°	-59.80°	Non
Reflex	92.00	6.60°	-61.30°	Non	Reflex	191.00	4.70°	-59.80°	Non
Reflex	95.00	7.00°	-61.20°	Non	Reflex	194.00	4.20°	-59.60°	Non
Reflex	98.00	6.60°	-61.10°	Non	Reflex	197.00	4.70°	-59.40°	Non
Reflex	101.00	7.20°	-61.20°	Non	Reflex	200.00	4.60°	-59.20°	Non
Reflex	104.00	6.80°	-61.20°	Non	Reflex	203.00	4.40°	-59.00°	Non
Reflex	107.00	5.60°	-61.10°	Non	Reflex	206.00	6.00°	-58.70°	Oui
Reflex	110.00	5.30°	-60.90°	Non	Reflex	209.00	5.80°	-58.30°	Non
Reflex	113.00	5.30°	-60.80°	Non	Reflex	212.00	6.40°	-57.90°	Non
Reflex	116.00	5.10°	-60.80°	Non	Reflex	215.00	6.70°	-57.70°	Non
Reflex	119.00	5.00°	-60.70°	Non	Reflex	218.00	6.90°	-57.60°	Non
Reflex	122.00	5.30°	-60.70°	Non	Reflex	221.00	9.00°	-57.60°	Oui
Reflex	125.00	5.40°	-60.60°	Non	Reflex	224.00	6.30°	-57.40°	Non
Reflex	128.00	5.20°	-60.50°	Non	Reflex	227.00	7.20°	-57.30°	Non
Reflex	131.00	5.50°	-60.40°	Non	Reflex	230.00	5.90°	-57.30°	Non
Reflex	134.00	5.40°	-60.40°	Non	Reflex	233.00	5.90°	-57.20°	Non
Reflex	137.00	5.30°	-60.30°	Non	Reflex	236.00	5.80°	-57.20°	Non
Reflex	140.00	6.70°	-60.20°	Non	Reflex	239.00	5.60°	-57.20°	Non
Reflex	143.00	6.80°	-60.30°	Non	Reflex	242.00	5.30°	-57.00°	Non
Reflex	146.00	6.50°	-60.20°	Non	Reflex	245.00	5.10°	-56.80°	Non
Reflex	149.00	6.40°	-60.10°	Non	Reflex	248.00	5.00°	-56.60°	Non
Reflex	152.00	6.50°	-60.10°	Non	Reflex	251.00	4.80°	-56.60°	Non
Reflex	155.00	6.60°	-60.20°	Non	Reflex	254.00	4.60°	-56.50°	Non
Reflex	158.00	6.80°	-60.20°	Non	Reflex	257.00	4.30°	-56.30°	Non
Reflex	161.00	6.90°	-60.20°	Non	Reflex	260.00	4.20°	-56.20°	Non
Reflex	164.00	6.50°	-60.20°	Non	Reflex	263.00	3.80°	-56.20°	Non
Reflex	167.00	6.70°	-60.10°	Non	Reflex	266.00	3.70°	-56.10°	Non
Reflex	170.00	7.20°	-60.10°	Oui	Reflex	269.00	3.90°	-55.90°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	3.80°	-55.80°	Non	Reflex	371.00	2.40°	-53.60°	Non
Reflex	275.00	4.20°	-55.70°	Non	Reflex	374.00	3.80°	-53.50°	Non
Reflex	278.00	4.50°	-55.90°	Non	Reflex	377.00	4.90°	-53.40°	Non
Reflex	281.00	4.00°	-55.90°	Non	Reflex	380.00	4.20°	-53.40°	Non
Reflex	284.00	3.60°	-55.80°	Non	Reflex	383.00	4.40°	-53.30°	Non
Reflex	287.00	3.10°	-55.60°	Non	Reflex	386.00	6.50°	-53.30°	Non
Reflex	290.00	2.50°	-55.40°	Non	Reflex	389.00	6.50°	-53.20°	Non
Reflex	293.00	1.60°	-55.40°	Non	Reflex	392.00	8.30°	-53.20°	Non
Reflex	296.00	2.30°	-55.40°	Non	Reflex	395.00	9.10°	-53.10°	Non
Reflex	299.00	2.50°	-55.40°	Non	Reflex	398.00	6.40°	-53.10°	Non
Reflex	302.00	3.20°	-55.40°	Non	Reflex	401.00	4.40°	-53.10°	Oui
Reflex	305.00	3.00°	-55.30°	Non	Reflex	404.00	7.40°	-53.10°	Non
Reflex	308.00	3.60°	-55.20°	Non	Reflex	407.00	5.10°	-53.00°	Non
Reflex	311.00	5.20°	-55.20°	Oui	Reflex	410.00	7.00°	-53.00°	Non
Reflex	314.00	4.10°	-55.20°	Non	Reflex	413.00	8.10°	-53.00°	Non
Reflex	317.00	4.30°	-55.10°	Non	Reflex	416.00	8.40°	-52.90°	Non
Reflex	320.00	6.20°	-55.10°	Non	Reflex	419.00	6.10°	-52.90°	Non
Reflex	323.00	5.90°	-55.10°	Non	Reflex	422.00	7.40°	-52.80°	Non
Reflex	326.00	6.20°	-55.00°	Non	Reflex	425.00	7.70°	-52.70°	Non
Reflex	329.00	6.70°	-55.00°	Non	Reflex	428.00	7.70°	-52.60°	Non
Reflex	332.00	6.70°	-55.00°	Non	Reflex	431.00	7.70°	-52.60°	Non
Reflex	335.00	4.00°	-54.90°	Non	Reflex	434.00	6.80°	-52.50°	Non
Reflex	338.00	4.60°	-54.80°	Non	Reflex	437.00	7.30°	-52.30°	Non
Reflex	341.00	4.60°	-54.70°	Non	Reflex	440.00	4.70°	-52.10°	Non
Reflex	344.00	3.70°	-54.60°	Non	Reflex	443.00	4.80°	-52.00°	Non
Reflex	347.00	6.80°	-54.50°	Non	Reflex	446.00	5.80°	-51.90°	Non
Reflex	350.00	6.90°	-54.40°	Non	Reflex	449.00	1.90°	-51.80°	Oui
Reflex	353.00	5.60°	-54.30°	Non	Reflex	452.00	4.10°	-51.70°	Non
Reflex	356.00	5.80°	-54.20°	Non					
Reflex	359.00	5.00°	-54.10°	Non					
Reflex	362.00	5.10°	-54.00°	Non					
Reflex	365.00	4.50°	-53.90°	Non					
Reflex	368.00	3.50°	-53.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	6.00	MT						
		<b>Mort-terrain</b>						
6.00	71.10	GA	6.00	7.50	D011942	1.50	<0.005	0.001
		<b>Gabbro 15°</b>	7.50	9.00	D011943	1.50	<0.005	0.001
		Massive, fortement carbonaté et chloritisé, localement hématisée, présence de fuschite par endroit.	9.00	10.50	D011944	1.50	<0.005	0.001
			10.50	12.00	D011946	1.50	<0.005	0.001
			12.00	13.50	D011947	1.50	<0.005	0.001
			13.50	15.00	D011948	1.50	<0.005	0.001
			15.00	16.50	D011949	1.50	<0.005	0.001
			16.50	18.00	D011950	1.50	<0.005	0.001
			18.00	19.50	D011951	1.50	<0.005	0.001
			19.50	21.00	D011952	1.50	<0.005	0.001
			21.00	22.50	D011953	1.50	<0.005	0.001
			22.50	24.00	D011954	1.50	<0.005	0.001
			24.00	25.50	D011956	1.50	<0.005	0.001
			25.50	27.00	D011957	1.50	<0.005	0.001
			27.00	28.50	D011958	1.50	<0.005	0.001
			28.50	30.00	D011959	1.50	<0.005	0.001
			30.00	31.50	D011960	1.50	<0.005	0.001
			31.50	33.00	D011961	1.50	<0.005	0.001
			33.00	34.50	D011962	1.50	<0.005	0.001
			34.50	36.00	D011963	1.50	0.017	0.017
			36.00	37.50	D011964	1.50	<0.005	0.001
			37.50	39.00	D011966	1.50	<0.005	0.001
			39.00	40.50	D011967	1.50	<0.005	0.001
			40.50	42.00	D011968	1.50	<0.005	0.001
			42.00	43.50	D011969	1.50	<0.005	0.001
			43.50	45.00	D011970	1.50	<0.005	0.001
			45.00	46.50	D011971	1.50	<0.005	0.001
			46.50	48.00	D011972	1.50	<0.005	0.001
			48.00	49.50	D011973	1.50	<0.005	0.001
			49.50	51.00	D011974	1.50	<0.005	0.001
			51.00	52.50	D011976	1.50	<0.005	0.001
			52.50	54.00	D011977	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
71.10	196.70	SY; POR <b>Syénite 50*; Porphyrique</b> Syénite porphyrique hématisée, séricitisée par endroit, localement magnétique.	54.00	55.50	D011978	1.50	<0.005		0.001
			55.50	57.00	D011979	1.50	<0.005		0.001
			57.00	58.50	D011980	1.50	<0.005		0.001
			58.50	60.00	D011981	1.50	<0.005		0.001
			60.00	61.50	D011982	1.50	<0.005		0.001
			61.50	63.00	D011983	1.50	<0.005		0.001
			63.00	64.50	D011984	1.50	<0.005		0.001
			64.50	66.00	D011986	1.50	<0.005		0.001
			66.00	67.50	D011987	1.50	<0.005		0.001
			67.50	69.00	D011988	1.50	<0.005		0.001
			69.00	70.00	D011989	1.00	<0.005		0.001
			70.00	71.10	D011990	1.10	<0.005		0.001
			71.10	72.50	D011991	1.40	<0.005		0.001
			72.50	74.00	D011992	1.50	<0.005		0.001
			74.00	75.50	D011993	1.50	<0.005		0.001
			75.50	77.00	D011994	1.50	<0.005		0.001
			77.00	78.50	D011996	1.50	<0.005		0.001
			78.50	80.00	D011997	1.50	<0.005		0.001
			80.00	81.50	D011998	1.50	<0.005		0.001
			81.50	83.00	D011999	1.50	<0.005		0.001
			83.00	84.50	D012000	1.50	<0.005		0.001
			84.50	86.00	D012001	1.50	<0.005		0.001
			86.00	87.50	D012002	1.50	<0.005		0.001
			87.50	89.00	D012003	1.50	<0.005		0.001
			89.00	90.50	D012004	1.50	<0.005		0.001
			90.50	92.00	D012006	1.50	0.020		0.020
			92.00	93.50	D012007	1.50	0.006		0.006
			93.50	95.00	D012008	1.50	<0.005		0.001
			95.00	96.50	D012009	1.50	<0.005		0.001
			96.50	98.00	D012010	1.50	0.006		0.006
98.00	99.50	D012011	1.50	0.005		0.005			
99.50	101.00	D012012	1.50	0.011		0.011			
101.00	102.50	D012013	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	102.50	104.00	D012014	1.50	0.010		0.010
	104.00	105.50	D012016	1.50	0.112		0.112
	105.50	107.00	D012017	1.50	0.049		0.049
	107.00	108.50	D012018	1.50	0.095		0.095
	108.50	110.00	D012019	1.50	0.193		0.193
	110.00	111.50	D012020	1.50	0.319		0.319
	111.50	113.00	D012021	1.50	0.006		0.006
	113.00	114.50	D012022	1.50	0.038		0.038
	114.50	116.00	D012023	1.50	0.030		0.030
	116.00	117.50	D012024	1.50	<0.005		0.001
	117.50	119.00	D012026	1.50	0.024		0.024
	119.00	120.50	D012027	1.50	0.021		0.021
	120.50	122.00	D012028	1.50	0.044		0.044
	122.00	123.50	D012029	1.50	0.005		0.005
	123.50	125.00	D012030	1.50	0.044		0.044
	125.00	126.50	D012031	1.50	0.010		0.010
	126.50	128.00	D012032	1.50	0.050		0.050
	128.00	129.50	D012033	1.50	0.024		0.024
	129.50	131.00	D012034	1.50	0.045		0.045
	131.00	132.50	D012036	1.50	<0.005		0.001
	132.50	134.00	D012037	1.50	0.017		0.017
	134.00	135.50	D012038	1.50	0.026		0.026
	135.50	137.00	D012039	1.50	0.039		0.039
	137.00	138.50	D012040	1.50	0.026		0.026
	138.50	140.00	D012041	1.50	0.051		0.051
	140.00	141.50	D012042	1.50	0.005		0.005
	141.50	143.00	D012043	1.50	0.008		0.008
	143.00	144.50	D012044	1.50	<0.005		0.001
	144.50	146.00	D012046	1.50	0.013		0.013
	146.00	147.50	D012047	1.50	0.007		0.007
	147.50	149.00	D012048	1.50	<0.005		0.001
	149.00	150.50	D012049	1.50	0.007		0.007
	150.50	152.00	D012050	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	152.00	153.50	D012051	1.50	<0.005		0.001	
	153.50	155.00	D012052	1.50	<0.005		0.001	
	155.00	156.50	D012053	1.50	<0.005		0.001	
	156.50	158.00	D012054	1.50	<0.005		0.001	
	158.00	159.50	D012056	1.50	<0.005		0.001	
	159.50	161.00	D012057	1.50	<0.005		0.001	
	161.00	162.50	D012058	1.50	<0.005		0.001	
	162.50	164.00	D012059	1.50	0.017		0.017	
	164.00	165.50	D012060	1.50	<0.005		0.001	
	165.50	167.00	D012061	1.50	0.092		0.092	
	167.00	168.50	D012062	1.50	0.078		0.078	
	168.50	170.00	D012063	1.50	0.034		0.034	
	170.00	171.50	D012064	1.50	0.011		0.011	
	171.50	173.00	D012066	1.50	0.017		0.017	
	173.00	174.50	D012067	1.50	0.006		0.006	
	174.50	176.00	D012068	1.50	0.006		0.006	
	176.00	177.50	D012069	1.50	<0.005		0.001	
	177.50	179.00	D012070	1.50	<0.005		0.001	
	179.00	180.50	D012071	1.50	<0.005		0.001	
	180.50	182.00	D012072	1.50	<0.005		0.001	
	182.00	183.50	D012073	1.50	<0.005		0.001	
	183.50	185.00	D012074	1.50	<0.005		0.001	
	185.00	186.50	D012076	1.50	<0.005		0.001	
	186.50	188.00	D012077	1.50	<0.005		0.001	
	188.00	189.50	D012078	1.50	<0.005		0.001	
	189.50	191.00	D012079	1.50	<0.005		0.001	
	191.00	192.50	D012080	1.50	<0.005		0.001	
	192.50	194.00	D012081	1.50	<0.005		0.001	
	194.00	195.50	D012082	1.50	<0.005		0.001	
	195.50	196.70	D012083	1.20	<0.005		0.001	
196.70	279.40	GA						
		<b>Gabbro 40*</b>						
		gabbro à leucocène, silicifié, bréchifié avec beaucoup de fuschite sur						
		9 derniers mètres.						
			196.70	198.00	D012084	1.30	<0.005	0.001
			198.00	199.50	D012086	1.50	<0.005	0.001
			199.50	201.00	D012087	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	201.00	202.50	D012088	1.50	<0.005		0.001
	202.50	204.00	D012089	1.50	<0.005		0.001
	204.00	205.50	D012090	1.50	<0.005		0.001
	205.50	207.00	D012091	1.50	<0.005		0.001
	207.00	208.50	D012092	1.50	<0.005		0.001
	208.50	210.00	D012093	1.50	<0.005		0.001
	210.00	211.50	D012094	1.50	<0.005		0.001
	211.50	213.00	D012096	1.50	<0.005		0.001
	213.00	214.50	D012097	1.50	0.006		0.006
	214.50	216.00	D012098	1.50	<0.005		0.001
	216.00	217.50	D012099	1.50	<0.005		0.001
	217.50	219.20	D012100	1.70	0.009		0.009
	219.20	220.90	D012101	1.70	0.543		0.543
	220.90	222.50	D012102	1.60	<0.005		0.001
	222.50	224.00	D012103	1.50	0.009		0.009
	224.00	225.50	D012104	1.50	<0.005		0.001
	225.50	227.00	D012106	1.50	<0.005		0.001
	227.00	228.50	D012107	1.50	<0.005		0.001
	228.50	230.00	D012108	1.50	<0.005		0.001
	230.00	231.50	D012109	1.50	<0.005		0.001
	231.50	233.00	D012110	1.50	0.235		0.235
	233.00	234.50	D012111	1.50	<0.005		0.001
	234.50	236.00	D012112	1.50	<0.005		0.001
	236.00	237.50	D012113	1.50	<0.005		0.001
	237.50	239.00	D012114	1.50	<0.005		0.001
	239.00	240.50	D012116	1.50	<0.005		0.001
	240.50	242.00	D012117	1.50	<0.005		0.001
	242.00	243.50	D012118	1.50	<0.005		0.001
	243.50	245.00	D012119	1.50	<0.005		0.001
	245.00	246.50	D012120	1.50	<0.005		0.001
	246.50	248.00	D012121	1.50	<0.005		0.001
	248.00	249.50	D012122	1.50	<0.005		0.001
	249.50	251.00	D012123	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			251.00	252.50	D012124	1.50	<0.005		0.001
			252.50	254.00	D012126	1.50	<0.005		0.001
			254.00	255.50	D012127	1.50	<0.005		0.001
			255.50	257.00	D012128	1.50	<0.005		0.001
			257.00	258.50	D012129	1.50	<0.005		0.001
			258.50	260.00	D012130	1.50	<0.005		0.001
			260.00	261.50	D012131	1.50	0.027		0.027
			261.50	263.00	D012132	1.50	<0.005		0.001
			263.00	264.50	D012133	1.50	<0.005		0.001
			264.50	266.00	D012134	1.50	<0.005		0.001
			266.00	267.50	D012136	1.50	<0.005		0.001
			267.50	269.00	D012137	1.50	0.008		0.008
			269.00	270.50	D012138	1.50	1.290		1.290
			270.50	272.00	D012139	1.50	0.889		0.889
			272.00	273.50	D012140	1.50	0.176		0.176
			273.50	275.00	D012141	1.50	0.081		0.081
			275.00	276.50	D012142	1.50	2.940		2.940
			276.50	277.90	D012143	1.40	0.013		0.013
			277.90	279.50	D012144	1.60	0.005		0.005
279.40	452.00	SY; POR	279.50	281.00	D012146	1.50	<0.005		0.001
		<b>Syénite; Porphyrique</b>	281.00	282.50	D012147	1.50	0.144		0.144
		Syénite porphyrique carbonaté et hématisée, localement bréchifiée.	282.50	284.00	D012148	1.50	0.038		0.038
			284.00	285.50	D012149	1.50	0.027		0.027
			285.50	287.00	D012150	1.50	0.175		0.175
			287.00	288.50	D012151	1.50	<0.005		0.001
			288.50	290.00	D012152	1.50	0.172		0.172
			290.00	291.50	D012153	1.50	0.293		0.293
			291.50	293.00	D012154	1.50	0.201		0.201
			293.00	294.50	D012156	1.50	0.170		0.170
			294.50	296.00	D012157	1.50	0.513		0.513
			296.00	297.50	D012158	1.50	0.367		0.367
			297.50	299.00	D012159	1.50	0.573		0.573
			299.00	300.50	D012160	1.50	0.071		0.071

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	300.50	302.00	D012161	1.50	0.048		0.048
	302.00	303.50	D012162	1.50	0.107		0.107
	303.50	305.00	D012163	1.50	0.214		0.214
	305.00	306.50	D012164	1.50	1.275		1.275
	306.50	308.00	D012166	1.50	1.040		1.040
	308.00	309.50	D012167	1.50	0.069		0.069
	309.50	311.00	D012168	1.50	<0.005		0.001
	311.00	312.50	D012169	1.50	<0.005		0.001
	312.50	314.00	D012170	1.50	0.032		0.032
	314.00	315.50	D012171	1.50	<0.005		0.001
	315.50	317.00	D012172	1.50	0.045		0.045
	317.00	318.50	D012173	1.50	<0.005		0.001
	318.50	320.00	D012174	1.50	0.059		0.059
	320.00	321.50	D012176	1.50	0.105		0.105
	321.50	323.00	D012177	1.50	0.258		0.258
	323.00	324.50	D012178	1.50	0.028		0.028
	324.50	326.00	D012179	1.50	0.700		0.700
	326.00	327.50	D012180	1.50	0.525		0.525
	327.50	329.00	D012181	1.50	2.420		2.420
	329.00	330.50	D012182	1.50	0.931		0.931
	330.50	332.00	D012183	1.50	0.174		0.174
	332.00	333.50	D012184	1.50	<0.005		0.001
	333.50	335.00	D012186	1.50	<0.005		0.001
	335.00	336.50	D012187	1.50	0.025		0.025
	336.50	338.00	D012188	1.50	<0.005		0.001
	338.00	339.50	D012189	1.50	<0.005		0.001
	339.50	341.00	D012190	1.50	<0.005		0.001
	341.00	342.50	D012191	1.50	<0.005		0.001
	342.50	344.00	D012192	1.50	<0.005		0.001
	344.00	345.50	D012193	1.50	0.007		0.007
	345.50	347.00	D012194	1.50	<0.005		0.001
	347.00	348.50	D012196	1.50	<0.005		0.001
	348.50	350.00	D012197	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	350.00	351.50	D012198	1.50	<0.005		0.001
	351.50	353.00	D012199	1.50	<0.005		0.001
	353.00	354.50	D012200	1.50	<0.005		0.001
	354.50	356.00	D012201	1.50	<0.005		0.001
	356.00	357.50	D012202	1.50	<0.005		0.001
	357.50	359.00	D012203	1.50	<0.005		0.001
	359.00	360.50	D012204	1.50	0.042		0.042
	360.50	362.00	D012206	1.50	<0.005		0.001
	362.00	363.50	D012207	1.50	0.130		0.130
	363.50	365.00	D012208	1.50	<0.005		0.001
	365.00	366.50	D012209	1.50	<0.005		0.001
	366.50	368.00	D012210	1.50	<0.005		0.001
	368.00	369.50	D012211	1.50	<0.005		0.001
	369.50	371.00	D012212	1.50	<0.005		0.001
	371.00	372.50	D012213	1.50	0.091		0.091
	372.50	374.00	D012214	1.50	0.143		0.143
	374.00	375.50	D012216	1.50	0.059		0.059
	375.50	377.00	D012217	1.50	0.101		0.101
	377.00	378.50	D012218	1.50	0.137		0.137
	378.50	380.00	D012219	1.50	1.840		1.840
	380.00	381.70	D012220	1.70	0.875		0.875
	381.70	383.40	D012221	1.70	0.040		0.040
	383.40	385.00	D012222	1.60	0.026		0.026
	385.00	386.50	D012223	1.50	<0.005		0.001
	386.50	388.00	D012224	1.50	<0.005		0.001
	388.00	389.50	D012226	1.50	0.020		0.020
	389.50	391.00	D012227	1.50	<0.005		0.001
	391.00	392.50	D012228	1.50	0.067		0.067
	392.50	394.00	D012229	1.50	<0.005		0.001
	394.00	395.50	D012230	1.50	<0.005		0.001
	395.50	397.00	D012231	1.50	<0.005		0.001
	397.00	398.50	D012232	1.50	<0.005		0.001
	398.50	400.00	D012233	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	400.00	401.50	D012234	1.50	<0.005		0.001
	401.50	403.00	D012236	1.50	<0.005		0.001
	403.00	404.50	D012237	1.50	0.012		0.012
	404.50	406.00	D012238	1.50	<0.005		0.001
	406.00	407.50	D012239	1.50	0.230		0.230
	407.50	409.00	D012240	1.50	0.028		0.028
	409.00	410.50	D012241	1.50	<0.005		0.001
	410.50	412.00	D012242	1.50	<0.005		0.001
	412.00	413.50	D012243	1.50	<0.005		0.001
	413.50	415.00	D012244	1.50	0.017		0.017
	415.00	416.50	D012246	1.50	<0.005		0.001
	416.50	418.00	D012247	1.50	<0.005		0.001
	418.00	419.50	D012248	1.50	<0.005		0.001
	419.50	421.00	D012249	1.50	<0.005		0.001
	421.00	422.50	D012250	1.50	<0.005		0.001
	422.50	424.00	D012251	1.50	<0.005		0.001
	424.00	425.50	D012252	1.50	<0.005		0.001
	425.50	427.00	D012253	1.50	0.018		0.018
	427.00	428.50	D012254	1.50	<0.005		0.001
	428.50	430.00	D012256	1.50	<0.005		0.001
	430.00	431.50	D012257	1.50	<0.005		0.001
	431.50	433.00	D012258	1.50	<0.005		0.001
	433.00	434.50	D012259	1.50	<0.005		0.001
	434.50	436.00	D012260	1.50	<0.005		0.001
	436.00	437.50	D012261	1.50	<0.005		0.001
	437.50	439.00	D012262	1.50	<0.005		0.001
	439.00	440.70	D012263	1.70	0.037		0.037
	440.70	442.40	D012264	1.70	0.529		0.529
	442.40	444.00	D012266	1.60	0.009		0.009
	444.00	445.00	D012267	1.00	0.225		0.225
	445.00	446.70	D012268	1.70	0.773		0.773
	446.70	448.40	D012269	1.70	1.115		1.115
	448.40	450.00	D012270	1.60	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	450.00	451.00	D012271	1.00	<0.005		0.001
	451.00	452.00	D012272	1.00	<0.005		0.001
<p>452.00      Fin du sondage                      Nombre d'échantillons : 298                      Nombre d'échantillons QAQC : 33                      Longueur totale échantillonnée : 446.00</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.00	10.50	D011945	H	1.50	0.984	0.984
22.50	24.00	D011955	D011954	1.50	<0.005	0.001
34.50	36.00	D011965	A3	1.50	0.597	0.597
49.50	51.00	D011975	D011974	1.50	<0.005	0.001
61.50	63.00	D011985	M1	1.50	<0.005	0.001
75.50	77.00	D011995	D011994	1.50	<0.005	0.001
87.50	89.00	D012005	B4	1.50	2.610	2.610
102.50	104.00	D012015	D012014	1.50	0.009	0.009
114.50	116.00	D012025	M1	1.50	<0.005	0.001
129.50	131.00	D012035	D012034	1.50	0.044	0.044
141.50	143.00	D012045	C4	1.50	1.335	1.335
156.50	158.00	D012055	D012054	1.50	0.015	0.015
168.50	170.00	D012065	M1	1.50	<0.005	0.001
183.50	185.00	D012075	D012074	1.50	<0.005	0.001
195.50	196.70	D012085	D2	1.20	0.818	0.818
210.00	211.50	D012095	D012094	1.50	<0.005	0.001
224.00	225.50	D012105	M1	1.50	<0.005	0.001
237.50	239.00	D012115	D012114	1.50	<0.005	0.001
249.50	251.00	D012125	F2	1.50	8.180	8.450
264.50	266.00	D012135	D012134	1.50	<0.005	0.001
276.50	277.90	D012145	M1	1.40	<0.005	0.001
291.50	293.00	D012155	D012154	1.50	0.187	0.187
305.00	306.50	D012165	G2	1.50	4.010	3.970
318.50	320.00	D012175	D012174	1.50	0.063	0.063
332.00	333.50	D012185	H	1.50	0.750	0.750
345.50	347.00	D012195	D012194	1.50	<0.005	0.001
359.00	360.50	D012205	B4	1.50	2.590	2.590
372.50	374.00	D012215	D012214	1.50	0.129	0.129
386.50	388.00	D012225	M1	1.50	<0.005	0.001
400.00	401.50	D012235	D012234	1.50	<0.005	0.001
412.00	413.50	D012245	C4	1.50	1.325	1.325
427.00	428.50	D012255	D012254	1.50	<0.005	0.001
440.70	442.40	D012265	M1	1.70	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-149**

Titre minier :

Section :                      630 900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Ciara Cooke

Lot :

Du :                              2010-04-04

Date de description :

Au :                              2010-04-11

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -69.00°  
 Longueur :                      427.70 m

Est	630 900.1
Nord	5 374 199.9
Élévation	300.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	102.00°	-69.80°	Oui
Reflex	5.00	100.50°	-69.80°	Oui
Reflex	8.00	100.30°	-69.80°	Oui
Reflex	11.00	359.00°	-69.50°	Oui
Reflex	14.00	359.00°	-69.50°	Non
Reflex	17.00	358.50°	-69.60°	Non
Reflex	20.00	358.90°	-69.70°	Non
Reflex	23.00	357.70°	-67.80°	Oui
Reflex	26.00	358.60°	-69.40°	Non
Reflex	29.00	358.80°	-69.50°	Non
Reflex	32.00	358.80°	-69.30°	Non
Reflex	35.00	358.90°	-69.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.30°	-69.30°	Non
Reflex	41.00	359.40°	-69.20°	Non
Reflex	44.00	359.60°	-69.20°	Non
Reflex	47.00	359.80°	-69.10°	Non
Reflex	50.00	359.70°	-68.90°	Non
Reflex	53.00	0.30°	-69.30°	Non
Reflex	56.00	0.30°	-69.30°	Non
Reflex	59.00	0.70°	-69.40°	Non
Reflex	62.00	1.10°	-69.30°	Non
Reflex	65.00	1.40°	-69.50°	Non
Reflex	68.00	1.90°	-69.50°	Non
Reflex	71.00	2.20°	-69.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.50°	-69.50°	Non
Reflex	77.00	2.80°	-69.50°	Non
Reflex	80.00	3.30°	-69.60°	Non
Reflex	83.00	3.80°	-69.50°	Non
Reflex	86.00	4.30°	-69.40°	Non
Reflex	89.00	4.90°	-69.50°	Non
Reflex	92.00	5.80°	-69.80°	Non
Reflex	95.00	6.50°	-69.50°	Non
Reflex	98.00	7.30°	-69.40°	Non
Reflex	101.00	7.40°	-69.30°	Non
Reflex	104.00	7.30°	-69.30°	Non
Reflex	107.00	7.50°	-69.30°	Non
Reflex	110.00	8.00°	-69.50°	Non
Reflex	113.00	7.70°	-69.20°	Non
Reflex	116.00	9.00°	-69.50°	Oui
Reflex	119.00	7.70°	-69.10°	Non
Reflex	122.00	7.80°	-69.20°	Non
Reflex	125.00	8.10°	-69.10°	Non
Reflex	128.00	8.00°	-69.20°	Non
Reflex	131.00	8.60°	-69.30°	Non
Reflex	134.00	8.40°	-69.00°	Non
Reflex	137.00	8.50°	-68.90°	Non
Reflex	140.00	8.60°	-68.90°	Non
Reflex	143.00	8.50°	-68.90°	Non
Reflex	146.00	8.60°	-68.70°	Non
Reflex	149.00	8.70°	-68.60°	Non
Reflex	152.00	8.80°	-68.70°	Non
Reflex	155.00	8.80°	-68.40°	Non
Reflex	158.00	8.70°	-68.30°	Non
Reflex	161.00	9.30°	-68.20°	Oui
Reflex	164.00	8.90°	-68.20°	Non
Reflex	167.00	8.70°	-68.10°	Non
Reflex	170.00	9.10°	-68.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	9.20°	-68.00°	Non
Reflex	176.00	8.50°	-68.00°	Non
Reflex	179.00	8.30°	-68.00°	Non
Reflex	182.00	9.80°	-68.00°	Oui
Reflex	185.00	8.70°	-68.00°	Non
Reflex	188.00	1.50°	-59.40°	Oui
Reflex	191.00	9.20°	-68.00°	Non
Reflex	194.00	7.90°	-68.00°	Non
Reflex	197.00	8.80°	-68.00°	Non
Reflex	200.00	9.90°	-68.00°	Non
Reflex	203.00	9.60°	-68.00°	Non
Reflex	206.00	9.60°	-68.00°	Non
Reflex	209.00	9.30°	-68.00°	Non
Reflex	212.00	9.70°	-68.00°	Non
Reflex	215.00	9.60°	-68.00°	Non
Reflex	218.00	9.50°	-67.90°	Non
Reflex	221.00	10.20°	-67.90°	Non
Reflex	224.00	9.90°	-67.80°	Non
Reflex	227.00	10.00°	-67.70°	Non
Reflex	230.00	9.70°	-67.70°	Non
Reflex	233.00	10.20°	-68.00°	Non
Reflex	236.00	9.80°	-67.60°	Non
Reflex	239.00	10.30°	-67.50°	Non
Reflex	242.00	9.80°	-67.30°	Non
Reflex	245.00	10.10°	-67.30°	Non
Reflex	248.00	10.40°	-67.40°	Non
Reflex	251.00	10.40°	-67.30°	Non
Reflex	254.00	10.40°	-67.30°	Non
Reflex	257.00	11.30°	-67.30°	Non
Reflex	260.00	10.20°	-67.10°	Non
Reflex	263.00	9.90°	-67.20°	Non
Reflex	266.00	9.60°	-67.20°	Non
Reflex	269.00	9.50°	-67.10°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	10.30°	-67.20°	Non	Reflex	371.00	10.00°	-60.30°	Oui
Reflex	275.00	10.30°	-67.10°	Non	Reflex	374.00	8.90°	-60.20°	Non
Reflex	278.00	11.60°	-67.10°	Non	Reflex	377.00	9.20°	-60.20°	Non
Reflex	281.00	11.00°	-67.00°	Non	Reflex	380.00	9.30°	-60.10°	Non
Reflex	284.00	14.10°	-66.90°	Oui	Reflex	383.00	9.70°	-60.00°	Non
Reflex	287.00	11.30°	-66.90°	Non	Reflex	386.00	10.00°	-59.80°	Non
Reflex	290.00	13.30°	-67.90°	Oui	Reflex	389.00	9.10°	-59.70°	Non
Reflex	293.00	11.20°	-66.80°	Non	Reflex	392.00	8.20°	-59.60°	Non
Reflex	296.00	11.40°	-66.60°	Non	Reflex	395.00	8.80°	-59.50°	Non
Reflex	299.00	10.60°	-66.30°	Oui	Reflex	398.00	8.90°	-59.50°	Non
Reflex	302.00	11.30°	-66.60°	Non	Reflex	401.00	9.00°	-59.40°	Non
Reflex	305.00	11.10°	-66.50°	Non	Reflex	404.00	9.50°	-59.30°	Non
Reflex	308.00	11.00°	-66.40°	Non	Reflex	407.00	10.00°	-59.20°	Non
Reflex	311.00	10.10°	-65.90°	Non	Reflex	410.00	8.60°	-59.10°	Non
Reflex	314.00	9.90°	-65.50°	Non	Reflex	413.00	11.40°	-59.00°	Oui
Reflex	317.00	9.70°	-64.90°	Non	Reflex	416.00	10.60°	-58.90°	Non
Reflex	320.00	8.80°	-64.50°	Non	Reflex	419.00	10.50°	-58.80°	Non
Reflex	323.00	8.10°	-63.90°	Non	Reflex	422.00	10.10°	-58.70°	Non
Reflex	326.00	8.30°	-63.20°	Non	Reflex	425.00	12.10°	-58.60°	Non
Reflex	329.00	7.50°	-62.30°	Non					
Reflex	332.00	8.20°	-61.90°	Non					
Reflex	335.00	9.40°	-61.40°	Non					
Reflex	338.00	10.90°	-60.80°	Oui					
Reflex	341.00	7.00°	-59.20°	Non					
Reflex	344.00	7.80°	-60.70°	Non					
Reflex	347.00	8.80°	-60.60°	Non					
Reflex	350.00	8.50°	-60.50°	Non					
Reflex	353.00	7.90°	-60.50°	Non					
Reflex	356.00	8.40°	-60.30°	Non					
Reflex	359.00	8.60°	-60.50°	Non					
Reflex	362.00	8.70°	-60.50°	Non					
Reflex	365.00	8.60°	-60.40°	Non					
Reflex	368.00	8.60°	-60.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.00	MT						
		<b>Mort-terrain</b>						
5.00	93.30	GA; MAS	5.00	6.50	D012500	1.50	<0.005	0.001
		<b>Gabbro 25°; Roche massive</b>						
		Gabbro à leucocène fortement carbonaté, localement épidotisé.						
			6.50	8.00	D012501	1.50	<0.005	0.001
			8.00	9.50	D012502	1.50	<0.005	0.001
			9.50	11.00	D012503	1.50	<0.005	0.001
			11.00	12.60	D012504	1.60	<0.005	0.001
			14.00	15.50	D012506	1.50	<0.005	0.001
			15.50	17.00	D012507	1.50	<0.005	0.001
			17.00	18.50	D012508	1.50	<0.005	0.001
			20.00	21.50	D012509	1.50	<0.005	0.001
			21.50	23.00	D012510	1.50	<0.005	0.001
			23.00	24.50	D012511	1.50	<0.005	0.001
			24.50	26.00	D012512	1.50	<0.005	0.001
			26.00	27.50	D012513	1.50	<0.005	0.001
			27.50	29.00	D012514	1.50	0.005	0.005
			29.00	30.50	D012516	1.50	<0.005	0.001
			30.50	32.00	D012517	1.50	<0.005	0.001
			32.00	33.50	D012518	1.50	<0.005	0.001
			33.50	35.00	D012519	1.50	<0.005	0.001
			35.00	36.50	D012521	1.50	<0.005	0.001
			36.50	38.00	D012522	1.50	<0.005	0.001
			38.00	39.50	D012523	1.50	<0.005	0.001
			39.50	41.00	D012524	1.50	<0.005	0.001
			41.00	42.50	D012526	1.50	<0.005	0.001
			42.50	44.00	D012527	1.50	<0.005	0.001
			44.00	45.50	D012528	1.50	<0.005	0.001
			45.50	47.00	D012529	1.50	0.033	0.033
			47.00	48.50	D012530	1.50	0.005	0.005
			48.50	50.00	D012531	1.50	0.006	0.006
			50.00	51.50	D012532	1.50	<0.005	0.001
			51.50	53.00	D012533	1.50	<0.005	0.001
			53.00	54.50	D012534	1.50	<0.005	0.001
			54.50	56.00	D012536	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			56.00	57.50	D012537	1.50	<0.005	0.001
			57.50	59.00	D012538	1.50	<0.005	0.001
			59.00	60.50	D012539	1.50	<0.005	0.001
			60.50	62.00	D012540	1.50	<0.005	0.001
			62.00	63.50	D012541	1.50	<0.005	0.001
			63.50	65.00	D012542	1.50	<0.005	0.001
			65.00	66.50	D012543	1.50	<0.005	0.001
			66.50	68.00	D012544	1.50	<0.005	0.001
			68.00	69.50	D012546	1.50	<0.005	0.001
			69.50	71.00	D012547	1.50	<0.005	0.001
			71.00	72.50	D012548	1.50	0.005	0.005
			72.50	74.00	D012549	1.50	0.006	0.006
			74.00	75.50	D012550	1.50	0.005	0.005
			75.50	77.00	D012551	1.50	<0.005	0.001
			77.00	78.50	D012552	1.50	<0.005	0.001
			78.50	80.00	D012553	1.50	0.006	0.006
			80.00	81.50	D012554	1.50	<0.005	0.001
			81.50	83.00	D012556	1.50	0.005	0.005
			83.00	84.50	D012557	1.50	<0.005	0.001
			84.50	86.00	D012558	1.50	<0.005	0.001
			86.00	87.50	D012559	1.50	<0.005	0.001
			87.50	89.00	D012561	1.50	<0.005	0.001
			89.00	90.50	D012562	1.50	0.005	0.005
			90.50	92.00	D012563	1.50	0.007	0.007
			92.00	93.35	D012564	1.35	<0.005	0.001
93.30	95.20	SY <b>Syénite 20°</b> Syénite massive carbonaté, séricitisée et faiblement hématisée.	93.35	94.30	D012566	0.95	<0.005	0.001
			94.30	95.20	D012567	0.90	0.005	0.005
95.20	96.10	GA; MAS <b>Gabbro 20°; Roche massive</b> Carbonaté, chloritisé et séricitisé.	95.20	96.10	D012568	0.90	<0.005	0.001
96.10	283.00	SY <b>Syénite 25°</b> Localement massive, localement porphyrique, hématisée, localement séricitisée, parfois magnétique.	96.10	97.50	D012569	1.40	0.005	0.005
			97.50	99.00	D012570	1.50	<0.005	0.001
			99.00	100.00	D012571	1.00	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	100.00	101.50	D012572	1.50	<0.005		0.001
	101.50	103.00	D012573	1.50	<0.005		0.001
	103.00	104.50	D012574	1.50	0.005		0.005
	104.50	106.00	D012576	1.50	0.007		0.007
	106.00	107.50	D012577	1.50	0.005		0.005
	107.50	109.00	D012578	1.50	0.007		0.007
	109.00	110.50	D012579	1.50	0.006		0.006
	110.50	112.00	D012580	1.50	0.007		0.007
	112.00	113.50	D012581	1.50	0.007		0.007
	113.50	115.00	D012582	1.50	0.007		0.007
	115.00	116.50	D012583	1.50	0.005		0.005
	116.50	118.00	D012584	1.50	<0.005		0.001
	118.00	119.50	D012586	1.50	0.005		0.005
	119.50	121.00	D012587	1.50	<0.005		0.001
	121.00	122.50	D012588	1.50	<0.005		0.001
	122.50	124.00	D012589	1.50	0.005		0.005
	124.00	125.50	D012590	1.50	0.007		0.007
	125.50	127.00	D012591	1.50	0.067		0.067
	127.00	128.50	D012592	1.50	0.055		0.055
	128.50	130.00	D012593	1.50	0.034		0.034
	130.00	131.50	D012594	1.50	0.009		0.009
	131.50	133.00	D012596	1.50	0.010		0.010
	133.00	134.50	D012597	1.50	0.005		0.005
	134.50	136.00	D012598	1.50	0.030		0.030
	136.00	137.50	D012599	1.50	<0.005		0.001
	137.50	139.00	D012600	1.50	0.016		0.016
	139.00	140.50	D012601	1.50	0.005		0.005
	140.50	142.00	D012602	1.50	0.005		0.005
	142.00	143.50	D012603	1.50	0.005		0.005
	143.50	145.00	D012604	1.50	<0.005		0.001
	145.00	146.50	D012606	1.50	<0.005		0.001
	146.50	148.00	D012607	1.50	<0.005		0.001
	148.00	149.50	D012608	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	149.50	151.00	D012609	1.50	<0.005		0.001
	151.00	152.50	D012610	1.50	0.008		0.008
	152.50	154.00	D012611	1.50	<0.005		0.001
	154.00	155.50	D012612	1.50	<0.005		0.001
	155.50	157.00	D012613	1.50	<0.005		0.001
	157.00	158.50	D012614	1.50	0.026		0.026
	158.50	160.00	D012616	1.50	0.024		0.024
	160.00	161.50	D012617	1.50	0.221		0.221
	161.50	163.00	D012618	1.50	0.016		0.016
	163.00	164.50	D012619	1.50	0.029		0.029
	164.50	166.00	D012620	1.50	0.025		0.025
	166.00	167.50	D012621	1.50	0.017		0.017
	167.50	169.00	D012622	1.50	0.026		0.026
	169.00	170.50	D012623	1.50	0.009		0.009
	170.50	172.00	D012624	1.50	0.006		0.006
	172.00	173.50	D012626	1.50	0.009		0.009
	173.50	175.00	D012627	1.50	0.038		0.038
	175.00	176.50	D012628	1.50	<0.005		0.001
	176.50	178.00	D012629	1.50	0.020		0.020
	178.00	179.50	D012630	1.50	0.005		0.005
	179.50	181.00	D012631	1.50	0.036		0.036
	181.00	182.50	D012632	1.50	0.110		0.110
	182.50	184.00	D012633	1.50	0.014		0.014
	184.00	185.50	D012634	1.50	<0.005		0.001
	185.50	187.00	D012636	1.50	0.018		0.018
	187.00	188.50	D012637	1.50	0.016		0.016
	188.50	190.00	D012638	1.50	0.008		0.008
	190.00	191.50	D012639	1.50	0.006		0.006
	191.50	193.00	D012641	1.50	0.241		0.241
	193.00	194.50	D012642	1.50	0.139		0.139
	194.50	196.00	D012643	1.50	0.009		0.009
	196.00	197.50	D012644	1.50	3.120		3.120
	197.50	199.00	D012646	1.50	2.230		2.230

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	199.00	200.50	D012647	1.50	0.007		0.007
	200.50	202.00	D012648	1.50	0.245		0.245
	202.00	203.50	D012649	1.50	0.147		0.147
	203.50	205.00	D012650	1.50	1.225		1.225
	205.00	206.50	D012651	1.50	0.110		0.110
	206.50	208.00	D012652	1.50	2.240		2.240
	208.00	209.50	D012653	1.50	1.950		1.950
	209.50	211.00	D012654	1.50	0.690		0.690
	211.00	212.50	D012656	1.50	0.055		0.055
	212.50	214.00	D012657	1.50	0.543		0.543
	214.00	215.50	D012658	1.50	0.028		0.028
	215.50	217.00	D012659	1.50	0.014		0.014
	217.00	218.50	D012660	1.50	0.016		0.016
	218.50	220.00	D012661	1.50	0.012		0.012
	220.00	221.50	D012662	1.50	0.032		0.032
	221.50	223.00	D012663	1.50	0.040		0.040
	223.00	224.50	D012664	1.50	0.069		0.069
	224.50	226.00	D012666	1.50	0.023		0.023
	226.00	227.50	D012667	1.50	0.048		0.048
	227.50	229.00	D012668	1.50	0.261		0.261
	229.00	230.50	D012669	1.50	0.413		0.413
	230.50	232.00	D012670	1.50	0.005		0.005
	232.00	233.50	D012671	1.50	0.018		0.018
	233.50	235.00	D012672	1.50	<0.005		0.001
	235.00	236.50	D012673	1.50	<0.005		0.001
	236.50	237.50	D012674	1.00	<0.005		0.001
	237.50	238.70	D012676	1.20	0.007		0.007
	238.70	240.00	D012677	1.30	<0.005		0.001
	240.00	241.00	D012678	1.00	<0.005		0.001
	241.00	242.40	D012679	1.40	<0.005		0.001
	242.40	244.00	D012681	1.60	0.011		0.011
	244.00	245.50	D012682	1.50	<0.005		0.001
	245.50	247.00	D012683	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			247.00	248.50	D012684	1.50	<0.005		0.001
			248.50	250.00	D012686	1.50	0.012		0.012
			250.00	251.50	D012687	1.50	<0.005		0.001
			251.50	253.00	D012688	1.50	0.007		0.007
			253.00	254.50	D012689	1.50	0.010		0.010
			254.50	256.00	D012690	1.50	0.007		0.007
			256.00	257.50	D012691	1.50	0.007		0.007
			257.50	259.00	D012692	1.50	0.010		0.010
			259.00	260.50	D012693	1.50	<0.005		0.001
			260.50	262.00	D012694	1.50	<0.005		0.001
			262.00	263.50	D012696	1.50	<0.005		0.001
			263.50	265.00	D012697	1.50	<0.005		0.001
			265.00	266.50	D012698	1.50	<0.005		0.001
			266.50	268.00	D012699	1.50	<0.005		0.001
			268.00	269.50	D012700	1.50	<0.005		0.001
			269.50	271.00	D012701	1.50	<0.005		0.001
			271.00	272.50	D012702	1.50	<0.005		0.001
			272.50	274.00	D012703	1.50	<0.005		0.001
			274.00	275.50	D012704	1.50	<0.005		0.001
			275.50	277.00	D012706	1.50	<0.005		0.001
			277.00	278.50	D012707	1.50	<0.005		0.001
			278.50	280.00	D012708	1.50	<0.005		0.001
			280.00	281.50	D012709	1.50	<0.005		0.001
			281.50	283.00	D012710	1.50	0.045		0.045
283.00	340.20	GA; MAS	283.00	284.50	D012711	1.50	<0.005		0.001
		<b>Gabbro 30°; Roche massive</b>	284.50	286.00	D012712	1.50	<0.005		0.001
		Massive gabbro, chlorite and sericite alteration, locally hematized, locally porphyritic.	286.00	287.50	D012713	1.50	<0.005		0.001
			287.50	289.00	D012714	1.50	<0.005		0.001
			289.00	290.50	D012716	1.50	<0.005		0.001
			290.50	292.00	D012717	1.50	<0.005		0.001
			292.00	293.50	D012718	1.50	<0.005		0.001
			293.50	295.00	D012719	1.50	<0.005		0.001
			295.00	296.50	D012721	1.50	<0.005		0.001





Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	346.50	348.00	D012759	1.50	0.006		0.006
	348.00	349.50	D012761	1.50	<0.005		0.001
	349.50	351.00	D012762	1.50	0.005		0.005
	351.00	352.50	D012763	1.50	0.006		0.006
	352.50	354.00	D012764	1.50	0.006		0.006
	354.00	355.00	D012766	1.00	0.005		0.005
	355.00	356.50	D012767	1.50	0.031		0.031
	356.50	358.00	D012768	1.50	0.005		0.005
	358.00	359.50	D012769	1.50	0.005		0.005
	359.50	361.00	D012770	1.50	<0.005		0.001
	361.00	362.50	D012771	1.50	<0.005		0.001
	362.50	364.20	D012772	1.70	0.005		0.005
	364.20	365.90	D012773	1.70	<0.005		0.001
	365.90	367.40	D012774	1.50	0.220		0.220
	367.40	368.90	D012776	1.50	0.037		0.037
	368.90	370.50	D012777	1.60	0.251		0.251
	370.50	372.10	D012778	1.60	0.256		0.256
	372.10	373.50	D012779	1.40	1.525		1.525
	373.50	375.00	D012780	1.50	4.160		4.160
	375.00	376.60	D012781	1.60	3.140		3.140
	376.60	378.00	D012782	1.40	1.135		1.135
	378.00	379.50	D012783	1.50	1.090		1.090
	379.50	381.00	D012784	1.50	1.745		1.745
	381.00	382.50	D012786	1.50	2.950		2.950
	382.50	384.10	D012787	1.60	4.930		4.930
	384.10	385.80	D012788	1.70	4.420		4.420
	385.80	387.50	D012789	1.70	0.429		0.429
	387.50	389.00	D012790	1.50	0.124		0.124
	389.00	390.50	D012791	1.50	0.203		0.203
	390.50	392.00	D012792	1.50	0.059		0.059
	392.00	393.70	D012793	1.70	0.068		0.068
	393.70	395.40	D012794	1.70	0.393		0.393
	395.40	397.00	D012796	1.60	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	397.00	398.50	D012797	1.50	0.006		0.006
	398.50	400.00	D012798	1.50	<0.005		0.001
	400.00	401.50	D012799	1.50	<0.005		0.001
	401.50	403.00	D012801	1.50	0.007		0.007
	403.00	404.50	D012802	1.50	0.170		0.170
	404.50	406.00	D012803	1.50	0.054		0.054
	406.00	407.50	D012804	1.50	0.010		0.010
	407.50	409.00	D012806	1.50	0.009		0.009
	409.00	410.50	D012807	1.50	<0.005		0.001
	410.50	412.00	D012808	1.50	0.007		0.007
	412.00	413.50	D012809	1.50	<0.005		0.001
	413.50	415.00	D012810	1.50	<0.005		0.001
	415.00	416.50	D012811	1.50	<0.005		0.001
	416.50	418.00	D012812	1.50	0.006		0.006
	418.00	419.50	D012813	1.50	0.005		0.005
	419.50	421.00	D012814	1.50	0.023		0.023
	421.00	422.50	D012816	1.50	0.227		0.227
	422.50	424.00	D012817	1.50	<0.005		0.001
	424.00	425.50	D012818	1.50	0.021		0.021
	425.50	426.50	D012819	1.00	0.188		0.188
	426.50	427.70	D012820	1.20	<0.005		0.001
427.70	Fin du sondage Nombre d'échantillons : 282 Nombre d'échantillons QAQC : 39 Longueur totale échantillonnée : 419.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
11.00	12.60	D012505	D012504	1.60	<0.005	0.001
27.50	27.50	D012515	B4	0.00	2.560	2.560
33.50	33.50	D012520	M1	0.00	<0.005	0.001
39.50	41.00	D012525	D012524	1.50	<0.005	0.001
53.00	53.00	D012535	C4	0.00	1.350	1.350
66.50	68.00	D012545	D012544	1.50	<0.005	0.001
80.00	80.00	D012555	D2	0.00	0.868	0.868
86.00	86.00	D012560	M1	0.00	<0.005	0.001
92.00	93.35	D012565	D012564	1.35	<0.005	0.001
103.00	103.00	D012575	F2	0.00	8.320	8.320
116.50	118.00	D012585	D012584	1.50	0.006	0.006
130.00	130.00	D012595	H	0.00	0.980	0.980
143.50	145.00	D012605	D012604	1.50	<0.005	0.001
157.00	157.00	D012615	A3	0.00	0.599	0.599
170.50	172.00	D012625	D012624	1.50	0.006	0.006
184.00	184.00	D012635	B4	0.00	2.600	2.600
190.00	190.00	D012640	M1	0.00	0.006	0.006
196.00	197.50	D012645	D012644	1.50	3.050	3.050
209.50	209.50	D012655	C4	0.00	1.365	1.365
223.00	224.50	D012665	D012664	1.50	0.055	0.055
236.50	236.50	D012675	D2	0.00	0.883	0.883
241.00	241.00	D012680	M1	0.00	<0.005	0.001
247.00	248.50	D012685	D012684	1.50	<0.005	0.001
260.50	260.50	D012695	F2	0.00	8.350	8.350
274.00	275.50	D012705	D012704	1.50	<0.005	0.001
287.50	287.50	D012715	H	0.00	0.936	0.936
293.50	293.50	D012720	M1	0.00	<0.005	0.001
299.50	301.00	D012725	D012724	1.50	<0.005	0.001
313.00	313.00	D012735	A3	0.00	0.584	0.584
326.50	328.00	D012745	D012744	1.50	0.047	0.047
340.20	340.20	D012755	B4	0.00	2.710	2.710
346.50	346.50	D012760	M1	0.00	<0.005	0.001
352.50	354.00	D012765	D012764	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
365.90	365.90	D012775	C4	0.00	1.360	1.360
379.50	381.00	D012785	D012784	1.50	1.630	1.630
393.70	393.70	D012795	D2	0.00	0.982	0.982
400.00	400.00	D012800	M1	0.00	<0.005	0.001
406.00	407.50	D012805	D012804	1.50	0.010	0.010
419.50	419.50	D012815	F2	0.00	8.450	8.450

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-150**

Titre minier :

Section :                      630700

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :            Gilles.KAMTA

Du :                      2010-03-25

Date de description :

Au :                     2010-03-27

Collet

Azimut :                357.00°  
 Plongée :               -60.00°  
 Longueur :            241.61 m

UTM

Est	630 705.2
Nord	5 374 499.8
Élévation	309.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	12.20°	-60.40°	Oui
Reflex	5.00	1.70°	-60.30°	Oui
Reflex	8.00	359.10°	-60.30°	Oui
Reflex	11.00	2.90°	-60.30°	Non
Reflex	14.00	2.20°	-60.30°	Non
Reflex	17.00	2.90°	-60.30°	Non
Reflex	20.00	1.70°	-60.30°	Non
Reflex	23.00	0.50°	-60.30°	Non
Reflex	26.00	359.90°	-60.40°	Non
Reflex	29.00	1.40°	-60.30°	Non
Reflex	32.00	1.00°	-60.50°	Non
Reflex	35.00	1.70°	-60.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.20°	-60.40°	Non
Reflex	41.00	359.80°	-60.40°	Non
Reflex	44.00	1.00°	-60.50°	Non
Reflex	47.00	1.20°	-60.50°	Non
Reflex	50.00	2.80°	-60.60°	Oui
Reflex	53.00	1.80°	-60.60°	Non
Reflex	56.00	3.10°	-60.70°	Non
Reflex	59.00	4.00°	-60.80°	Non
Reflex	62.00	3.40°	-60.80°	Non
Reflex	65.00	1.70°	-60.80°	Non
Reflex	68.00	2.60°	-60.80°	Non
Reflex	71.00	1.30°	-60.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.90°	-60.90°	Non	Reflex	173.00	4.30°	-61.30°	Non
Reflex	77.00	358.90°	-60.90°	Non	Reflex	176.00	4.90°	-61.40°	Non
Reflex	80.00	0.30°	-61.00°	Non	Reflex	179.00	3.60°	-61.30°	Non
Reflex	83.00	359.70°	-61.10°	Non	Reflex	182.00	4.10°	-61.20°	Non
Reflex	86.00	3.30°	-61.10°	Non	Reflex	185.00	3.40°	-61.20°	Non
Reflex	89.00	3.80°	-61.10°	Non	Reflex	188.00	7.40°	-61.10°	Non
Reflex	92.00	3.30°	-61.00°	Non	Reflex	191.00	7.30°	-61.00°	Non
Reflex	95.00	3.60°	-61.00°	Non	Reflex	194.00	6.80°	-61.00°	Non
Reflex	98.00	2.40°	-61.10°	Non	Reflex	197.00	4.00°	-61.10°	Non
Reflex	101.00	359.70°	-61.10°	Non	Reflex	200.00	5.00°	-61.10°	Non
Reflex	104.00	359.70°	-61.10°	Non	Reflex	203.00	5.00°	-61.10°	Non
Reflex	107.00	357.80°	-61.00°	Non	Reflex	206.00	5.00°	-61.10°	Non
Reflex	110.00	2.70°	-61.10°	Non	Reflex	209.00	4.90°	-61.10°	Non
Reflex	113.00	4.70°	-61.10°	Oui	Reflex	212.00	4.90°	-61.10°	Non
Reflex	116.00	0.70°	-61.30°	Oui	Reflex	215.00	5.10°	-61.10°	Non
Reflex	119.00	3.00°	-61.30°	Non	Reflex	218.00	5.20°	-61.10°	Non
Reflex	122.00	2.70°	-61.30°	Non	Reflex	221.00	5.30°	-61.00°	Non
Reflex	125.00	4.90°	-61.40°	Non	Reflex	224.00	5.50°	-61.00°	Non
Reflex	128.00	5.60°	-61.30°	Non	Reflex	227.00	5.70°	-61.00°	Non
Reflex	131.00	5.30°	-61.30°	Non	Reflex	230.00	5.80°	-61.00°	Non
Reflex	134.00	2.30°	-61.40°	Oui	Reflex	233.00	5.80°	-60.90°	Non
Reflex	137.00	4.80°	-61.30°	Non	Reflex	236.00	5.70°	-60.80°	Non
Reflex	140.00	2.60°	-61.30°	Oui					
Reflex	143.00	4.50°	-61.30°	Non					
Reflex	146.00	4.60°	-61.30°	Non					
Reflex	149.00	5.90°	-61.30°	Non					
Reflex	152.00	3.50°	-61.30°	Oui					
Reflex	155.00	5.40°	-61.30°	Non					
Reflex	158.00	3.40°	-61.30°	Oui					
Reflex	161.00	5.50°	-61.40°	Non					
Reflex	164.00	2.80°	-61.40°	Oui					
Reflex	167.00	5.00°	-61.30°	Non					
Reflex	170.00	2.10°	-61.30°	Oui					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.50	MT						
		<b>Mort-terrain</b>						
0.50	241.60	SY; MAS; FIN; MTY	0.50	2.00	D001733	1.50	<0.005	0.001
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	2.00	3.50	D001734	1.50	<0.005	0.001
		massive, quelques phénocristaux de FP automorphe blanchâtre maclé	3.50	5.00	D001735	1.50	0.006	0.006
		ou localement chloritisé, séricitisé et potassique, oxyde de carbonates,	5.00	6.50	D001736	1.50	<0.005	0.001
		hématisation, veine de QZ carbonaté 40-90° ac, cheveux et veinules	6.50	8.00	D001737	1.50	0.027	0.027
		QZ carbonaté 20-60° ac, oxydes de carbonates, PY automorphe et	8.00	8.90	D001738	0.90	<0.005	0.001
		fine	8.90	10.50	D001739	1.60	0.023	0.023
			10.50	12.00	D001740	1.50	<0.005	0.001
			12.00	13.50	D001741	1.50	<0.005	0.001
			13.50	15.00	D001743	1.50	<0.005	0.001
			15.00	16.50	D001744	1.50	<0.005	0.001
			16.50	18.00	D001745	1.50	<0.005	0.001
			18.00	19.50	D001746	1.50	<0.005	0.001
			19.50	21.00	D001747	1.50	0.049	0.049
			21.00	22.50	D001748	1.50	0.010	0.010
			22.50	24.00	D001749	1.50	0.030	0.030
			24.00	25.50	D001750	1.50	0.020	0.020
			25.50	27.00	D001751	1.50	<0.005	0.001
			27.00	28.50	D001753	1.50	<0.005	0.001
			28.50	30.00	D001754	1.50	0.047	0.047
			30.00	31.50	D001755	1.50	0.032	0.032
			31.50	33.00	D001756	1.50	0.005	0.005
			33.00	34.50	D001757	1.50	0.023	0.023
			34.50	36.00	D001758	1.50	0.005	0.005
			36.00	37.50	D001759	1.50	0.006	0.006
			37.50	38.60	D001760	1.10	<0.005	0.001
			38.60	40.00	D001761	1.40	<0.005	0.001
			40.00	41.50	D001763	1.50	<0.005	0.001
			41.50	43.00	D001764	1.50	<0.005	0.001
			43.00	44.50	D001765	1.50	0.013	0.013
			44.50	46.00	D001766	1.50	0.063	0.063
			46.00	47.50	D001767	1.50	0.182	0.182

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			47.50	49.00	D001768	1.50		0.151
			49.00	50.60	D001769	1.60		0.378
			50.60	52.00	D001770	1.40		<0.005
			52.00	53.50	D001771	1.50		<0.005
			53.50	55.00	D001773	1.50		<0.005
			55.00	56.50	D001774	1.50		0.203
			56.50	58.00	D001775	1.50		0.016
			58.00	59.50	D001776	1.50		0.098
			59.50	61.00	D001777	1.50		0.091
			61.00	62.50	D001778	1.50		0.032
			62.50	64.00	D001779	1.50		0.194
			64.00	65.50	D001780	1.50		0.023
			65.50	67.00	D001781	1.50		<0.005
			67.00	68.50	D001783	1.50		<0.005
			68.50	70.00	D001784	1.50		0.341
			70.00	71.50	D001785	1.50		0.296
			71.50	73.00	D001786	1.50		0.126
			73.00	74.50	D001787	1.50		0.217
			74.50	76.00	D001788	1.50		0.018
			76.00	77.00	D001789	1.00		<0.005
			77.00	78.00	D001790	1.00		0.006
			78.00	79.50	D001791	1.50		0.055
			79.50	81.00	D001793	1.50		0.009
			81.00	82.50	D001794	1.50		0.011
			82.50	84.00	D001795	1.50		0.065
			84.00	85.50	D001796	1.50		<0.005
			85.50	87.00	D001797	1.50		<0.005
			87.00	88.50	D001798	1.50		<0.005
0.50	8.90	SY; MAS; POR <b>Syénite; Roche massive; Porphyrique</b> phénocristaux 0.2-2 cm automorphe ou sub arrondi, altération potassique, hématisation, oxydes de carbonâtes						
88.50	114.00	SY; MAS; POR; FIN; MOY <b>Syénite; Roche massive; Porphyrique; Grains fins;</b> <b>Grains moyens</b>	88.50	90.00	D001799	1.50		0.005
			90.00	91.50	D001800	1.50		<0.005



Corporation Minière Osisko Div. Exploration

Description		Analyse					
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
phénocristaux automorphe de FP 0.2- 1cm, veines de Qz carbonatés, localement pseudo cataclase, HM+++ , K++ , localement altération en calcite, PY fine diss	91.50	93.00	D001801	1.50	<0.005		0.001
	93.00	94.50	D001803	1.50	<0.005		0.001
	94.50	96.00	D001804	1.50	<0.005		0.001
	96.00	97.50	D001805	1.50	<0.005		0.001
	97.50	99.00	D001806	1.50	0.025		0.025
	99.00	100.50	D001807	1.50	<0.005		0.001
	100.50	102.00	D001808	1.50	<0.005		0.001
	102.00	103.50	D001809	1.50	0.006		0.006
	103.50	105.00	D001810	1.50	<0.005		0.001
	105.00	106.50	D001811	1.50	<0.005		0.001
	106.50	108.00	D001813	1.50	0.006		0.006
	108.00	109.50	D001814	1.50	<0.005		0.001
	109.50	111.00	D001815	1.50	<0.005		0.001
	111.00	112.50	D001816	1.50	0.009		0.009
	112.50	114.00	D001817	1.50	<0.005		0.001
	114.00	115.50	D001818	1.50	<0.005		0.001
	115.50	116.50	D001819	1.00	<0.005		0.001
	116.50	117.70	D001820	1.20	0.017		0.017
	117.70	119.00	D001821	1.30	0.023		0.023
	119.00	120.50	D001823	1.50	0.005		0.005
120.50	122.00	D001824	1.50	0.097		0.097	
122.00	123.50	D001825	1.50	0.005		0.005	
123.50	125.00	D001826	1.50	0.016		0.016	
125.00	126.50	D001827	1.50	0.009		0.009	
126.00	134.00	126.50	128.00	D001828	1.50	0.005	0.005
SY; MAS; POR; FIN <b>Syénite; Roche massive; Porphyrique; Grains fins</b> phénocristaux automorphe 30-40° ac, veinules carbonaté, cheveux 30° ac, K+++ , BO++ , xénolithe chloritisé	128.00	129.50	D001829	1.50	0.007		0.007
	129.50	131.00	D001830	1.50	<0.005		0.001
	131.00	132.50	D001831	1.50	<0.005		0.001
	132.50	134.00	D001833	1.50	<0.005		0.001
	134.00	135.50	D001834	1.50	0.017		0.017
	135.50	137.00	D001835	1.50	<0.005		0.001
	137.00	138.50	D001836	1.50	<0.005		0.001
	138.50	140.00	D001837	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
148.50	176.00	SY; MAS; FIN; POR <b>Syénite; Roche massive; Grains fins; Porphyrique</b> phénocristaux de FP 0.2-2 cm, veinules et cheveux de QZ et carbonâtes localement biotisé, altération en calcite, hématisation, chloriotisation, séricitisation, PY fine diss	140.00	141.50	D001838	1.50	<0.005		0.001
			141.50	143.00	D001839	1.50	<0.005		0.001
			143.00	144.50	D001840	1.50	<0.005		0.001
			144.50	146.00	D001841	1.50	<0.005		0.001
			146.00	147.50	D001843	1.50	<0.005		0.001
			147.50	149.00	D001844	1.50	<0.005		0.001
			149.00	150.50	D001845	1.50	<0.005		0.001
			150.50	152.00	D001846	1.50	<0.005		0.001
			152.00	153.50	D001847	1.50	0.024		0.024
			153.50	155.00	D001848	1.50	<0.005		0.001
			155.00	156.50	D001849	1.50	<0.005		0.001
			156.50	158.00	D001850	1.50	<0.005		0.001
			158.00	159.50	D001851	1.50	<0.005		0.001
			159.50	161.00	D001853	1.50	<0.005		0.001
			161.00	162.50	D001854	1.50	<0.005		0.001
			162.50	164.00	D001855	1.50	<0.005		0.001
			164.00	165.50	D001856	1.50	0.007		0.007
			165.50	167.00	D001857	1.50	0.007		0.007
			167.00	168.50	D001858	1.50	<0.005		0.001
			168.50	170.00	D001859	1.50	<0.005		0.001
			170.00	171.50	D001860	1.50	0.014		0.014
			171.50	173.00	D001861	1.50	<0.005		0.001
			173.00	174.50	D001863	1.50	0.027		0.027
			174.50	176.00	D001864	1.50	<0.005		0.001
			176.00	177.50	D001865	1.50	<0.005		0.001
			177.50	179.00	D001866	1.50	<0.005		0.001
			179.00	180.50	D001867	1.50	0.020		0.020
			180.50	182.00	D001868	1.50	0.031		0.031
182.00	183.50	D001869	1.50	<0.005		0.001			
183.50	185.00	D001870	1.50	0.007		0.007			
185.00	186.50	D001871	1.50	<0.005		0.001			
186.50	188.00	D001873	1.50	<0.005		0.001			
188.00	189.50	D001874	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
191.60	197.50	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> phénocristaux de feldspaths localement orienté 40-50° ac( pseudo trachytique), altération en calcite et potassique, SR+, CL+;	189.50	190.50	D001875	1.00	<0.005		0.001
			190.50	191.60	D001876	1.10	<0.005		0.001
			191.60	193.00	D001877	1.40	<0.005		0.001
			193.00	194.50	D001878	1.50	<0.005		0.001
			194.50	196.00	D001879	1.50	<0.005		0.001
			196.00	197.50	D001880	1.50	<0.005		0.001
			197.50	199.00	D001881	1.50	<0.005		0.001
			199.00	200.50	D001883	1.50	<0.005		0.001
			200.50	202.00	D001884	1.50	<0.005		0.001
			202.00	203.50	D001885	1.50	<0.005		0.001
			203.50	205.00	D001886	1.50	<0.005		0.001
			205.00	206.50	D001887	1.50	<0.005		0.001
			206.50	208.00	D001888	1.50	<0.005		0.001
			208.00	209.50	D001889	1.50	<0.005		0.001
			209.50	211.00	D001890	1.50	<0.005		0.001
			211.00	212.50	D001891	1.50	<0.005		0.001
			212.50	214.00	D001893	1.50	<0.005		0.001
			214.00	215.50	D001894	1.50	<0.005		0.001
			215.50	217.00	D001895	1.50	<0.005		0.001
			217.00	218.50	D001896	1.50	<0.005		0.001
			218.50	220.00	D001897	1.50	<0.005		0.001
			220.00	221.50	D001898	1.50	<0.005		0.001
			221.50	223.00	D001899	1.50	<0.005		0.001
223.00	224.50	D001900	1.50	<0.005		0.001			
224.50	226.00	D001901	1.50	<0.005		0.001			
226.00	227.50	D001905	1.50	<0.005		0.001			
227.50	229.00	D001906	1.50	<0.005		0.001			
229.00	230.50	D001907	1.50	<0.005		0.001			
230.50	232.00	D001908	1.50	<0.005		0.001			
232.00	233.50	D001909	1.50	0.010		0.010			
233.50	235.00	D001910	1.50	0.011		0.011			
235.00	236.50	D001911	1.50	<0.005		0.001			
236.50	238.00	D001913	1.50	0.055		0.055			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
241.60	241.61	OM Ouverture minière	238.00	239.50	D001914	1.50	0.089		0.089
			239.50	240.50	D001915	1.00	0.064		0.064
			240.50	241.60	D001916	1.10	0.180		0.180
241.61	Fin du sondage								
	Nombre d'échantillons : 164								
	Nombre d'échantillons QAQC : 18								
	Longueur totale échantillonnée : 241.10								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.00	13.50	D001742	D001741	1.50	<0.005	0.001
25.50	27.00	D001752	A3	1.50	0.617	0.617
38.60	40.00	D001762	D001761	1.40	0.013	0.013
52.00	53.50	D001772	M1	1.50	<0.005	0.001
65.50	67.00	D001782	D001781	1.50	<0.005	0.001
78.00	79.50	D001792	B4	1.50	2.560	2.560
91.50	93.00	D001802	D001801	1.50	<0.005	0.001
105.00	106.50	D001812	M1	1.50	<0.005	0.001
117.70	119.00	D001822	D001821	1.30	0.022	0.022
131.00	132.50	D001832	C4	1.50	1.085	1.085
144.50	146.00	D001842	D001841	1.50	<0.005	0.001
158.00	159.50	D001852	M1	1.50	<0.005	0.001
171.50	173.00	D001862	D001861	1.50	<0.005	0.001
185.00	186.50	D001872	D2	1.50	0.878	0.878
197.50	199.00	D001882	D001881	1.50	<0.005	0.001
211.00	212.50	D001892	M1	1.50	<0.005	0.001
224.50	226.00	D001902	D001901	1.50	<0.005	0.001
235.00	236.50	D001912	F2	1.50	8.170	8.490

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-151</b>	Titre minier :	Section :	631 200
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Guy Gbaguidi	Du : 2010-03-28	Date de description :	2010-04-25
	Au : 2010-04-02		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 470.00 m

UTM

Est	631 200.1
Nord	5 374 200.2
Élévation	305.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	6.60°	-60.40°	Oui
Reflex	5.00	0.10°	-60.20°	Non
Reflex	8.00	359.80°	-60.10°	Non
Reflex	11.00	359.80°	-60.00°	Non
Reflex	14.00	359.90°	-59.90°	Non
Reflex	17.00	360.00°	-59.80°	Non
Reflex	20.00	0.10°	-59.80°	Non
Reflex	23.00	0.20°	-59.70°	Non
Reflex	26.00	0.40°	-59.70°	Non
Reflex	29.00	0.60°	-59.70°	Non
Reflex	32.00	0.90°	-59.70°	Non
Reflex	35.00	1.00°	-59.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.00°	-59.50°	Non
Reflex	41.00	1.20°	-59.30°	Non
Reflex	44.00	1.00°	-59.20°	Non
Reflex	47.00	1.20°	-59.10°	Non
Reflex	50.00	1.30°	-59.10°	Non
Reflex	53.00	1.30°	-58.90°	Non
Reflex	56.00	1.20°	-58.60°	Non
Reflex	59.00	1.30°	-58.60°	Non
Reflex	62.00	1.10°	-58.40°	Non
Reflex	65.00	1.00°	-58.30°	Non
Reflex	68.00	1.10°	-58.40°	Non
Reflex	71.00	1.20°	-58.30°	Non

Description

Deux blocs 347; entre les blocs 359 et 362, 6.0 m de carotte

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.30°	-58.40°	Non	Reflex	173.00	3.80°	-58.30°	Non
Reflex	77.00	1.20°	-58.50°	Non	Reflex	176.00	3.70°	-58.20°	Non
Reflex	80.00	1.90°	-58.50°	Non	Reflex	179.00	3.70°	-58.20°	Non
Reflex	83.00	1.10°	-58.50°	Non	Reflex	182.00	3.70°	-58.20°	Non
Reflex	86.00	2.00°	-58.50°	Non	Reflex	185.00	3.90°	-58.20°	Non
Reflex	89.00	2.00°	-58.40°	Non	Reflex	188.00	3.90°	-58.20°	Non
Reflex	92.00	1.90°	-58.10°	Non	Reflex	191.00	4.00°	-58.20°	Non
Reflex	95.00	1.80°	-58.00°	Non	Reflex	194.00	4.00°	-58.20°	Non
Reflex	98.00	1.80°	-57.90°	Non	Reflex	197.00	4.00°	-58.20°	Non
Reflex	101.00	1.90°	-57.90°	Non	Reflex	200.00	4.00°	-58.20°	Non
Reflex	104.00	2.10°	-57.90°	Non	Reflex	203.00	3.90°	-58.20°	Non
Reflex	107.00	2.10°	-57.90°	Non	Reflex	206.00	3.90°	-58.10°	Non
Reflex	110.00	2.10°	-57.90°	Non	Reflex	209.00	3.70°	-58.10°	Non
Reflex	113.00	2.50°	-57.90°	Non	Reflex	212.00	6.50°	-58.00°	Oui
Reflex	116.00	2.30°	-57.90°	Non	Reflex	215.00	3.20°	-58.00°	Non
Reflex	119.00	2.50°	-57.90°	Non	Reflex	218.00	4.90°	-58.00°	Non
Reflex	122.00	2.50°	-57.90°	Non	Reflex	221.00	4.50°	-58.00°	Non
Reflex	125.00	2.60°	-57.90°	Non	Reflex	224.00	5.20°	-58.00°	Non
Reflex	128.00	2.70°	-58.10°	Non	Reflex	227.00	5.70°	-58.00°	Non
Reflex	131.00	2.70°	-58.10°	Non	Reflex	230.00	5.00°	-58.00°	Non
Reflex	134.00	2.80°	-58.10°	Non	Reflex	233.00	5.20°	-58.00°	Non
Reflex	137.00	2.90°	-58.10°	Non	Reflex	236.00	5.20°	-58.00°	Non
Reflex	140.00	2.80°	-58.10°	Non	Reflex	239.00	5.30°	-58.00°	Non
Reflex	143.00	2.90°	-58.20°	Non	Reflex	242.00	5.50°	-58.00°	Non
Reflex	146.00	3.00°	-58.20°	Non	Reflex	245.00	5.30°	-58.00°	Non
Reflex	149.00	3.30°	-58.20°	Non	Reflex	248.00	5.60°	-58.00°	Non
Reflex	152.00	3.20°	-58.20°	Non	Reflex	251.00	5.00°	-58.00°	Non
Reflex	155.00	3.20°	-58.20°	Non	Reflex	254.00	4.80°	-58.10°	Non
Reflex	158.00	3.50°	-58.20°	Non	Reflex	257.00	5.10°	-58.10°	Non
Reflex	161.00	5.70°	-58.20°	Oui	Reflex	260.00	5.90°	-58.10°	Non
Reflex	164.00	3.80°	-58.30°	Non	Reflex	263.00	5.40°	-58.10°	Non
Reflex	167.00	5.70°	-58.30°	Oui	Reflex	266.00	5.70°	-58.20°	Non
Reflex	170.00	3.90°	-58.30°	Non	Reflex	269.00	5.70°	-58.20°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.80°	-58.20°	Non	Reflex	371.00	7.80°	-58.30°	Non
Reflex	275.00	5.70°	-58.30°	Non	Reflex	374.00	7.80°	-58.30°	Non
Reflex	278.00	4.80°	-58.30°	Non	Reflex	377.00	7.80°	-58.30°	Non
Reflex	281.00	6.00°	-58.30°	Non	Reflex	380.00	8.20°	-58.20°	Non
Reflex	284.00	6.00°	-58.30°	Non	Reflex	383.00	7.90°	-58.20°	Non
Reflex	287.00	6.00°	-58.30°	Non	Reflex	386.00	7.90°	-58.20°	Non
Reflex	290.00	6.20°	-58.30°	Non	Reflex	389.00	8.00°	-58.30°	Non
Reflex	293.00	6.10°	-58.30°	Non	Reflex	392.00	10.30°	-58.30°	Oui
Reflex	296.00	6.30°	-58.30°	Non	Reflex	395.00	9.10°	-58.30°	Non
Reflex	299.00	6.30°	-58.30°	Non	Reflex	398.00	7.40°	-58.30°	Oui
Reflex	302.00	6.60°	-58.40°	Non	Reflex	401.00	10.30°	-58.30°	Non
Reflex	305.00	6.50°	-58.30°	Non	Reflex	404.00	5.10°	-58.30°	Non
Reflex	308.00	6.90°	-58.40°	Non	Reflex	407.00	7.80°	-58.40°	Non
Reflex	311.00	6.70°	-58.40°	Non	Reflex	410.00	7.60°	-58.30°	Non
Reflex	314.00	6.90°	-58.40°	Non	Reflex	413.00	8.20°	-58.30°	Non
Reflex	317.00	7.00°	-58.40°	Non	Reflex	416.00	8.60°	-58.30°	Non
Reflex	320.00	7.20°	-58.30°	Non	Reflex	419.00	8.40°	-58.40°	Non
Reflex	323.00	6.50°	-58.30°	Non	Reflex	422.00	7.50°	-58.40°	Non
Reflex	326.00	7.20°	-58.30°	Non	Reflex	425.00	10.60°	-58.30°	Non
Reflex	329.00	6.70°	-58.30°	Non	Reflex	428.00	8.00°	-58.30°	Non
Reflex	332.00	7.10°	-58.30°	Non	Reflex	431.00	8.40°	-58.30°	Non
Reflex	335.00	7.20°	-58.30°	Non	Reflex	434.00	6.90°	-58.30°	Non
Reflex	338.00	5.50°	-58.30°	Oui	Reflex	437.00	5.70°	-58.30°	Oui
Reflex	341.00	8.60°	-58.30°	Non	Reflex	440.00	6.80°	-58.40°	Non
Reflex	344.00	4.80°	-58.30°	Oui	Reflex	443.00	6.80°	-58.30°	Non
Reflex	347.00	6.70°	-58.40°	Non	Reflex	446.00	6.20°	-58.40°	Non
Reflex	350.00	6.80°	-58.40°	Non	Reflex	449.00	6.60°	-58.40°	Non
Reflex	353.00	6.70°	-58.30°	Non	Reflex	452.00	7.10°	-58.40°	Non
Reflex	356.00	6.70°	-58.30°	Non	Reflex	455.00	5.60°	-58.40°	Oui
Reflex	359.00	7.40°	-58.30°	Non	Reflex	458.00	7.00°	-58.40°	Non
Reflex	362.00	7.60°	-58.30°	Non	Reflex	461.00	6.70°	-58.40°	Non
Reflex	365.00	7.70°	-58.30°	Non	Reflex	464.00	6.80°	-58.40°	Non
Reflex	368.00	7.70°	-58.30°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT <b>Mort-terrain</b>						
2.50	14.10	SY; POR <b>Syénite 60°; Porphyrique</b> Syénite porphyrique séricitisée et localement bréchifiée.	2.50	4.00	D011589	1.50	<0.005	0.001
			4.00	5.50	D011590	1.50	0.011	0.011
			5.50	7.00	D011591	1.50	0.043	0.043
			7.00	8.60	D011592	1.60	1.110	1.110
			8.60	10.00	D011593	1.40	0.022	0.022
			10.00	11.50	D011594	1.50	0.007	0.007
			11.50	13.00	D011596	1.50	0.008	0.008
			13.00	14.10	D011597	1.10	0.009	0.009
14.10	24.40	BA <b>Basalte 60°</b> Basalte silicifié, hématisé chloritisée et séricitisé, localement bréchifié.	14.10	15.50	D011598	1.40	0.091	0.091
			15.50	17.00	D011599	1.50	0.012	0.012
			17.00	18.50	D011600	1.50	<0.005	0.001
			18.50	20.00	D011601	1.50	0.115	0.115
			20.00	21.50	D011602	1.50	0.586	0.586
			21.50	23.00	D011603	1.50	0.016	0.016
			23.00	24.40	D011604	1.40	5.480	5.07
24.40	50.00	SY; POR <b>Syénite 35°; Porphyrique</b> Syénite porphyrique séricitisée, localement épidotisée et silicifiée.	24.40	26.00	D011606	1.60	3.780	4.13
			26.00	27.50	D011607	1.50	0.452	0.452
			27.50	29.00	D011608	1.50	0.451	0.451
			29.00	30.20	D011609	1.20	0.079	0.079
			30.20	31.90	D011610	1.70	1.775	1.775
			31.90	33.50	D011611	1.60	0.921	0.921
			33.50	35.00	D011612	1.50	0.501	0.501
			35.00	36.40	D011613	1.40	0.184	0.184
			36.40	38.00	D011614	1.60	0.112	0.112
			38.00	39.50	D011616	1.50	0.025	0.025
			39.50	41.00	D011617	1.50	0.218	0.218
			41.00	42.50	D011618	1.50	0.038	0.038
			42.50	44.00	D011619	1.50	<0.005	0.001
			44.00	45.50	D011620	1.50	<0.005	0.001
			45.50	47.00	D011621	1.50	0.022	0.022
			47.00	48.50	D011622	1.50	0.079	0.079

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
50.00	118.50	BA <b>Basalte 20°</b> Basalte silicifié, hématisé, chloritisée et séricitisée, localement bréchifié, parfois complètement remplacé.	48.50	50.00	D011623	1.50	0.074	7.73	0.074
			50.00	51.00	D011624	1.00	7.300		7.730
			51.00	52.10	D011626	1.10	0.008		0.008
			52.10	53.50	D011627	1.40	0.008		0.008
			53.50	55.00	D011628	1.50	0.010		0.010
			55.00	56.50	D011629	1.50	0.030		0.030
			56.50	58.00	D011630	1.50	0.012		0.012
			58.00	59.50	D011631	1.50	<0.005		0.001
			59.50	61.00	D011632	1.50	0.007		0.007
			61.00	62.50	D011633	1.50	0.012		0.012
			62.50	64.00	D011634	1.50	0.308		0.308
			64.00	65.50	D011636	1.50	0.026		0.026
			65.50	67.00	D011637	1.50	0.006		0.006
			67.00	68.50	D011638	1.50	0.017		0.017
			68.50	70.00	D011639	1.50	0.193		0.193
			70.00	71.50	D011640	1.50	0.015		0.015
			71.50	73.00	D011641	1.50	0.027		0.027
			73.00	74.50	D011642	1.50	0.083		0.083
			74.50	76.00	D011643	1.50	0.020		0.020
			76.00	77.50	D011644	1.50	0.035		0.035
			77.50	79.00	D011646	1.50	0.009		0.009
			79.00	80.50	D011647	1.50	0.012		0.012
			80.50	82.00	D011648	1.50	0.280		0.280
			82.00	83.50	D011649	1.50	2.290		2.290
			83.50	85.00	D011650	1.50	0.014		0.014
			85.00	86.50	D011651	1.50	0.007		0.007
			86.50	88.00	D011652	1.50	0.006		0.006
88.00	89.50	D011653	1.50	<0.005	0.001				
89.50	91.00	D011654	1.50	<0.005	0.001				
91.00	92.50	D011656	1.50	<0.005	0.001				
92.50	93.90	D011657	1.40	0.005	0.005				
93.90	95.00	D011658	1.10	0.223	0.223				
95.00	96.00	D011659	1.00	0.010	0.010				

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			96.00	97.50	D011660	1.50	1.350		1.350
			97.50	99.00	D011661	1.50	0.005		0.005
			99.00	100.50	D011662	1.50	0.005		0.005
			100.50	102.00	D011663	1.50	0.005		0.005
			102.00	103.00	D011664	1.00	0.010		0.010
			103.00	104.50	D011666	1.50	0.187		0.187
			104.50	106.00	D011667	1.50	1.095		1.095
			106.00	107.50	D011668	1.50	2.340		2.340
			107.50	109.00	D011669	1.50	4.770	4.30	4.300
			109.00	110.60	D011670	1.60	2.730		2.730
			110.60	112.00	D011671	1.40	0.106		0.106
			112.00	113.00	D011672	1.00	0.006		0.006
			113.00	114.50	D011673	1.50	0.010		0.010
			114.50	116.00	D011674	1.50	0.024		0.024
			116.00	117.50	D011676	1.50	0.062		0.062
			117.50	118.50	D011677	1.00	0.016		0.016
118.50	127.60	SY; POR <b>Syénite 70°; Porphyrique</b> Syénite porphyrique hématisé, localement séricitisé avec des niveaux de texture trachytique.	118.50	120.00	D011678	1.50	0.025		0.025
			120.00	121.50	D011679	1.50	0.007		0.007
			121.50	123.00	D011680	1.50	0.089		0.089
			123.00	124.50	D011681	1.50	0.010		0.010
			124.50	126.00	D011682	1.50	0.213		0.213
			126.00	127.60	D011683	1.60	0.840		0.840
127.60	132.40	BA <b>Basalte</b> Chloritisé, silicifié, séricitisé, localement amygdalaire.	127.60	129.00	D011684	1.40	0.007		0.007
			129.00	130.00	D011686	1.00	0.009		0.009
			130.00	131.00	D011687	1.00	0.009		0.009
			131.00	132.40	D011688	1.40	0.010		0.010
132.40	172.70	SY; POR <b>Syénite 45°; Porphyrique</b> Hématisée, chloritisée, séricitisée, localement massive.	132.40	134.00	D011689	1.60	0.044		0.044
			134.00	135.50	D011690	1.50	<0.005		0.001
			135.50	137.00	D011691	1.50	<0.005		0.001
			137.00	138.50	D011692	1.50	0.412		0.412
			138.50	140.00	D011693	1.50	0.314		0.314
			140.00	141.50	D011694	1.50	0.045		0.045
			141.50	143.00	D011696	1.50	0.037		0.037

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			143.00	144.50	D011697	1.50		0.166	0.166
			144.50	146.00	D011698	1.50		0.011	0.011
			146.00	147.60	D011699	1.60		0.023	0.023
			147.60	149.00	D011700	1.40		0.031	0.031
			149.00	150.50	D011701	1.50		0.064	0.064
			150.50	152.00	D011702	1.50		0.061	0.061
			152.00	153.50	D011703	1.50		0.024	0.024
			153.50	155.00	D011704	1.50		0.022	0.022
			155.00	156.50	D011706	1.50		0.061	0.061
			156.50	158.00	D011707	1.50		0.021	0.021
			158.00	159.50	D011708	1.50		1.335	1.335
			159.50	161.00	D011709	1.50		<0.005	0.001
			161.00	162.50	D011710	1.50		0.005	0.005
			162.50	164.00	D011711	1.50		0.042	0.042
			164.00	165.60	D011712	1.60		<0.005	0.001
			165.60	167.00	D011713	1.40		<0.005	0.001
			167.00	168.50	D011714	1.50		0.006	0.006
			168.50	170.00	D011716	1.50		0.006	0.006
			170.00	171.50	D011717	1.50		<0.005	0.001
			171.50	172.70	D011718	1.20		0.020	0.020
172.70	226.30	BA; MAS; AMY	172.70	174.40	D011719	1.70		0.005	0.005
		<b>Basalte 45°; Roche massive; Amygdalaire</b>	174.40	176.00	D011720	1.60		<0.005	0.001
		Massive, séricitisé, localement silicifié, amygdalaire et hématisé avec la	176.00	177.50	D011721	1.50		<0.005	0.001
		profondeur.	177.50	179.00	D011722	1.50		<0.005	0.001
			179.00	180.50	D011723	1.50		<0.005	0.001
			180.50	182.00	D011724	1.50		<0.005	0.001
			182.00	183.50	D011726	1.50		<0.005	0.001
			183.50	185.00	D011727	1.50		<0.005	0.001
			185.00	186.50	D011728	1.50		<0.005	0.001
			186.50	188.00	D011729	1.50		<0.005	0.001
			188.00	189.50	D011730	1.50		0.019	0.019
			189.50	191.00	D011731	1.50		0.109	0.109
			191.00	192.50	D011732	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			192.50	194.00	D011733	1.50		0.047		0.047
			194.00	195.50	D011734	1.50		0.474		0.474
			195.50	197.00	D011736	1.50		<0.005		0.001
			197.00	198.50	D011737	1.50		<0.005		0.001
			198.50	200.00	D011738	1.50		<0.005		0.001
			200.00	201.50	D011739	1.50		<0.005		0.001
			201.50	203.00	D011740	1.50		<0.005		0.001
			203.00	204.50	D011741	1.50		<0.005		0.001
			204.50	206.00	D011742	1.50		<0.005		0.001
			206.00	207.50	D011743	1.50		<0.005		0.001
			207.50	209.00	D011744	1.50		<0.005		0.001
			209.00	210.50	D011746	1.50		<0.005		0.001
			210.50	212.00	D011747	1.50		<0.005		0.001
			212.00	213.50	D011748	1.50		<0.005		0.001
			213.50	215.00	D011749	1.50		<0.005		0.001
			215.00	216.50	D011750	1.50		<0.005		0.001
			216.50	218.00	D011751	1.50		<0.005		0.001
			218.00	219.50	D011752	1.50		<0.005		0.001
			219.50	221.00	D011753	1.50		<0.005		0.001
			221.00	222.50	D011754	1.50		<0.005		0.001
			222.50	224.00	D011756	1.50		<0.005		0.001
			224.00	225.00	D011757	1.00		<0.005		0.001
			225.00	226.30	D011758	1.30		<0.005		0.001
226.30	227.40	SY <b>Syénite 20*</b> Syénite séricitisée et hématisée.	226.30	227.40	D011759	1.10		0.028		0.028
227.40	245.50	BA; AMY <b>Basalte; Amygdalaire</b> Basalte amygdalaire localement hématisé et séricifisé, contact inf avec syénite irrég.	227.40	229.00	D011760	1.60		0.006		0.006
			229.00	230.50	D011761	1.50		0.008		0.008
			230.50	232.00	D011762	1.50		<0.005		0.001
			232.00	233.50	D011763	1.50		<0.005		0.001
			233.50	235.00	D011764	1.50		<0.005		0.001
			235.00	236.50	D011766	1.50		<0.005		0.001
			236.50	238.00	D011767	1.50		<0.005		0.001
			238.00	239.50	D011768	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
245.50	470.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique hématisée et localement carbonatée.	239.50	241.00	D011769	1.50	<0.005		0.001
			241.00	242.00	D011770	1.00	<0.005		0.001
			242.00	243.00	D011771	1.00	0.007		0.007
			243.00	244.50	D011772	1.50	0.408		0.408
			244.50	246.00	D011773	1.50	0.013		0.013
			246.00	247.50	D011774	1.50	<0.005		0.001
			247.50	249.00	D011776	1.50	0.005		0.005
			249.00	250.50	D011777	1.50	<0.005		0.001
			250.50	252.00	D011778	1.50	<0.005		0.001
			252.00	253.50	D011779	1.50	0.005		0.005
			253.50	255.00	D011780	1.50	0.013		0.013
			255.00	256.50	D011781	1.50	0.077		0.077
			256.50	258.00	D011782	1.50	0.006		0.006
			258.00	259.50	D011783	1.50	0.014		0.014
			259.50	261.00	D011784	1.50	0.012		0.012
			261.00	262.50	D011786	1.50	0.017		0.017
			262.50	264.00	D011787	1.50	0.005		0.005
			264.00	265.50	D011788	1.50	0.057		0.057
			265.50	267.00	D011789	1.50	0.009		0.009
			267.00	268.50	D011790	1.50	0.086		0.086
			268.50	270.00	D011791	1.50	0.229		0.229
			270.00	271.50	D011792	1.50	<0.005		0.001
			271.50	273.00	D011793	1.50	0.006		0.006
			273.00	274.50	D011794	1.50	0.010		0.010
			274.50	276.00	D011796	1.50	0.057		0.057
			276.00	277.50	D011797	1.50	0.094		0.094
			277.50	279.00	D011798	1.50	0.007		0.007
			279.00	280.50	D011799	1.50	0.151		0.151
			280.50	282.00	D011800	1.50	0.486		0.486
			282.00	283.50	D011801	1.50	0.101		0.101
283.50	285.00	D011802	1.50	0.079		0.079			
285.00	286.50	D011803	1.50	<0.005		0.001			
286.50	288.00	D011804	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	288.00	289.50	D011806	1.50	0.143		0.143
	289.50	291.00	D011807	1.50	0.220		0.220
	291.00	292.50	D011808	1.50	0.022		0.022
	292.50	294.00	D011809	1.50	0.070		0.070
	294.00	295.50	D011810	1.50	0.287		0.287
	295.50	297.00	D011811	1.50	0.065		0.065
	297.00	298.50	D011812	1.50	0.119		0.119
	298.50	300.00	D011813	1.50	0.081		0.081
	300.00	301.50	D011814	1.50	0.065		0.065
	301.50	303.00	D011816	1.50	0.053		0.053
	303.00	304.50	D011817	1.50	0.166		0.166
	304.50	306.00	D011818	1.50	0.014		0.014
	306.00	307.50	D011819	1.50	0.085		0.085
	307.50	309.00	D011820	1.50	0.041		0.041
	309.00	310.50	D011821	1.50	0.077		0.077
	310.50	312.00	D011822	1.50	0.052		0.052
	312.00	313.50	D011823	1.50	0.498		0.498
	313.50	315.00	D011824	1.50	0.168		0.168
	315.00	316.00	D011826	1.00	0.383		0.383
	316.00	317.40	D011827	1.40	0.706		0.706
	317.40	319.00	D011828	1.60	2.430		2.430
	319.00	320.50	D011829	1.50	0.583		0.583
	320.50	322.00	D011830	1.50	0.209		0.209
	322.00	323.50	D011831	1.50	0.064		0.064
	323.50	325.00	D011832	1.50	0.040		0.040
	325.00	326.50	D011833	1.50	0.035		0.035
	326.50	328.00	D011834	1.50	0.019		0.019
	328.00	329.50	D011836	1.50	0.241		0.241
	329.50	331.00	D011837	1.50	<0.005		0.001
	331.00	332.50	D011838	1.50	<0.005		0.001
	332.50	334.00	D011839	1.50	<0.005		0.001
	334.00	335.50	D011840	1.50	0.041		0.041
	335.50	337.00	D011841	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	337.00	338.50	D011842	1.50	<0.005		0.001
	338.50	340.00	D011843	1.50	0.014		0.014
	340.00	341.50	D011844	1.50	0.221		0.221
	341.50	343.00	D011846	1.50	0.005		0.005
	343.00	344.50	D011847	1.50	<0.005		0.001
	344.50	346.00	D011848	1.50	<0.005		0.001
	346.00	347.50	D011849	1.50	0.005		0.005
	347.50	349.00	D011850	1.50	<0.005		0.001
	349.00	350.50	D011851	1.50	<0.005		0.001
	350.50	352.00	D011852	1.50	<0.005		0.001
	352.00	353.50	D011853	1.50	<0.005		0.001
	353.50	355.00	D011854	1.50	0.028		0.028
	355.00	356.50	D011856	1.50	0.654		0.654
	356.50	358.00	D011857	1.50	0.072		0.072
	358.00	359.50	D011858	1.50	0.120		0.120
	359.50	361.00	D011859	1.50	0.181		0.181
	361.00	362.50	D011860	1.50	0.106		0.106
	362.50	364.00	D011861	1.50	0.123		0.123
	364.00	365.50	D011862	1.50	0.026		0.026
	365.50	367.00	D011863	1.50	0.005		0.005
	367.00	368.50	D011864	1.50	0.052		0.052
	368.50	369.80	D011866	1.30	0.116		0.116
	369.80	371.00	D011867	1.20	0.869		0.869
	371.00	372.70	D011868	1.70	1.065		1.065
	372.70	374.40	D011869	1.70	0.248		0.248
	374.40	376.00	D011870	1.60	0.103		0.103
	376.00	377.50	D011871	1.50	0.148		0.148
	377.50	379.00	D011872	1.50	0.355		0.355
	379.00	380.00	D011873	1.00	0.150		0.150
	380.00	381.00	D011874	1.00	0.083		0.083
	381.00	382.60	D011876	1.60	0.028		0.028
	382.60	384.00	D011877	1.40	0.795		0.795
	384.00	385.50	D011878	1.50	0.052		0.052



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	385.50	387.00	D011879	1.50	0.039		0.039
	387.00	388.50	D011880	1.50	0.298		0.298
	388.50	390.00	D011881	1.50	0.094		0.094
	390.00	391.50	D011882	1.50	0.745		0.745
	391.50	393.00	D011883	1.50	0.385		0.385
	393.00	394.50	D011884	1.50	1.800		1.800
	394.50	396.00	D011886	1.50	0.013		0.013
	396.00	397.50	D011887	1.50	0.249		0.249
	397.50	399.00	D011888	1.50	0.012		0.012
	399.00	400.50	D011889	1.50	0.355		0.355
	400.50	402.00	D011890	1.50	0.380		0.380
	402.00	403.50	D011891	1.50	0.071		0.071
	403.50	405.00	D011892	1.50	<0.005		0.001
	405.00	406.50	D011893	1.50	0.028		0.028
	406.50	408.00	D011894	1.50	0.039		0.039
	408.00	409.50	D011896	1.50	0.015		0.015
	409.50	411.00	D011897	1.50	0.381		0.381
	411.00	412.50	D011898	1.50	0.874		0.874
	412.50	414.00	D011899	1.50	1.005		1.005
	414.00	415.50	D011900	1.50	1.165		1.165
	415.50	417.00	D011901	1.50	0.692		0.692
	417.00	418.50	D011902	1.50	1.115		1.115
	418.50	420.00	D011903	1.50	0.354		0.354
	420.00	421.50	D011904	1.50	1.475		1.475
	421.50	423.00	D011906	1.50	0.805		0.805
	423.00	424.50	D011907	1.50	0.360		0.360
	424.50	426.00	D011908	1.50	2.020		2.020
	426.00	427.70	D011909	1.70	4.530	4.49	4.490
	427.70	429.30	D011910	1.60	1.310		1.310
	429.30	431.00	D011911	1.70	0.028		0.028
	431.00	432.50	D011912	1.50	0.006		0.006
	432.50	434.00	D011913	1.50	<0.005		0.001
	434.00	435.50	D011914	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	435.50	437.00	D011916	1.50	<0.005		0.001
	437.00	438.00	D011917	1.00	<0.005		0.001
	438.00	439.30	D011918	1.30	0.272		0.272
	439.30	441.00	D011919	1.70	0.010		0.010
	441.00	442.30	D011920	1.30	0.298		0.298
	442.30	444.00	D011921	1.70	0.098		0.098
	444.00	445.50	D011922	1.50	0.605		0.605
	445.50	447.00	D011923	1.50	0.015		0.015
	447.00	448.50	D011924	1.50	<0.005		0.001
	448.50	450.00	D011926	1.50	<0.005		0.001
	450.00	451.50	D011927	1.50	<0.005		0.001
	451.50	453.00	D011928	1.50	<0.005		0.001
	453.00	454.50	D011929	1.50	<0.005		0.001
	454.50	456.00	D011930	1.50	<0.005		0.001
	456.00	457.50	D011931	1.50	0.048		0.048
	457.50	459.00	D011932	1.50	0.112		0.112
	459.00	460.50	D011933	1.50	0.006		0.006
	460.50	462.00	D011934	1.50	0.010		0.010
	462.00	463.50	D011936	1.50	<0.005		0.001
	463.50	465.00	D011937	1.50	<0.005		0.001
	465.00	466.50	D011938	1.50	0.022		0.022
	466.50	468.00	D011939	1.50	<0.005		0.001
	468.00	469.00	D011940	1.00	<0.005		0.001
	469.00	470.00	D011941	1.00	<0.005		0.001
470.00	Fin du sondage Nombre d'échantillons : 318 Nombre d'échantillons QAQC : 35 Longueur totale échantillonnée : 467.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.00	11.50	D011595	D011594	1.50	0.006	0.006
23.00	23.00	D011605	D2	0.00	0.849	0.849
36.40	38.00	D011615	D011614	1.60	0.105	0.105
50.00	50.00	D011625	M1	0.00	0.006	0.006
62.50	64.00	D011635	D011634	1.50	0.310	0.310
76.00	76.00	D011645	F2	0.00	7.620	8.580
89.50	91.00	D011655	D011654	1.50	<0.005	0.001
102.00	102.00	D011665	M1	0.00	<0.005	0.001
114.50	116.00	D011675	D011674	1.50	0.021	0.021
127.60	127.60	D011685	G2	0.00	4.000	4.040
140.00	141.50	D011695	D011694	1.50	0.081	0.081
153.50	153.50	D011705	H	0.00	0.991	0.991
167.00	168.50	D011715	D011714	1.50	0.005	0.005
180.50	180.50	D011725	A3	0.00	0.626	0.626
194.00	195.50	D011735	D011734	1.50	0.418	0.418
207.50	207.50	D011745	M1	0.00	<0.005	0.001
221.00	222.50	D011755	D011754	1.50	<0.005	0.001
233.50	235.00	D011765	B4	1.50	2.630	2.630
246.00	247.50	D011775	D011774	1.50	0.005	0.005
259.50	259.50	D011785	M1	0.00	<0.005	0.001
273.00	274.50	D011795	D011794	1.50	0.010	0.010
286.50	286.50	D011805	C4	0.00	1.280	1.280
300.00	301.50	D011815	D011814	1.50	0.050	0.050
313.50	313.50	D011825	M1	0.00	<0.005	0.001
326.50	328.00	D011835	D011834	1.50	0.011	0.011
340.00	340.00	D011845	D2	0.00	0.871	0.871
353.50	355.00	D011855	D011854	1.50	<0.005	0.001
367.00	367.00	D011865	M1	0.00	<0.005	0.001
380.00	381.00	D011875	D011874	1.00	0.083	0.083
393.00	393.00	D011885	F2	0.00	8.220	8.340
406.50	408.00	D011895	D011894	1.50	0.040	0.040
420.00	420.00	D011905	M1	0.00	<0.005	0.001
434.00	435.50	D011915	D011914	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
447.00	447.00	D011925	G2	0.00	4.130	4.020
460.50	462.00	D011935	D011934	1.50	0.013	0.013

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-152**

Titre minier :

Section :                      631200

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-02

Date de description :      2010-04-22

Au :                      2010-04-06

Collet

UTM

Azimut :              0.00°

Plongée :             -68.00°

Longueur :          441.00 m

Est                      631 200.1

Nord                   5 374 200.0

Élévation             305.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	15.00°	-68.80°	Oui
Reflex	6.00	2.60°	-68.80°	Non
Reflex	9.00	3.00°	-68.80°	Non
Reflex	12.00	2.50°	-69.00°	Non
Reflex	15.00	2.40°	-68.60°	Non
Reflex	18.00	2.60°	-69.20°	Non
Reflex	21.00	1.60°	-67.70°	Oui
Reflex	24.00	3.00°	-68.90°	Non
Reflex	27.00	3.20°	-69.10°	Non
Reflex	30.00	3.10°	-68.90°	Non
Reflex	33.00	3.20°	-68.90°	Non
Reflex	36.00	3.40°	-69.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	3.10°	-68.90°	Non
Reflex	42.00	3.50°	-68.80°	Non
Reflex	45.00	3.70°	-68.90°	Non
Reflex	48.00	3.90°	-69.00°	Non
Reflex	51.00	3.90°	-69.10°	Non
Reflex	54.00	3.90°	-68.90°	Non
Reflex	57.00	4.00°	-68.90°	Non
Reflex	60.00	3.60°	-68.50°	Non
Reflex	63.00	4.00°	-68.80°	Non
Reflex	66.00	4.10°	-68.70°	Non
Reflex	69.00	4.10°	-68.60°	Non
Reflex	72.00	4.10°	-68.60°	Non

Description

Dimension de la carotte :

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	4.20°	-68.60°	Non
Reflex	78.00	4.20°	-68.50°	Non
Reflex	81.00	4.20°	-68.50°	Non
Reflex	84.00	4.40°	-68.60°	Non
Reflex	87.00	4.50°	-68.60°	Non
Reflex	90.00	4.30°	-68.60°	Non
Reflex	93.00	4.70°	-68.80°	Non
Reflex	96.00	5.00°	-68.50°	Non
Reflex	99.00	4.90°	-68.50°	Non
Reflex	102.00	5.10°	-68.80°	Non
Reflex	105.00	5.20°	-68.90°	Non
Reflex	108.00	5.20°	-68.70°	Non
Reflex	111.00	5.10°	-68.50°	Non
Reflex	114.00	7.40°	-70.40°	Oui
Reflex	117.00	4.80°	-68.20°	Non
Reflex	120.00	4.90°	-68.20°	Non
Reflex	123.00	5.10°	-68.20°	Non
Reflex	126.00	5.10°	-68.20°	Non
Reflex	129.00	5.10°	-68.20°	Non
Reflex	132.00	5.20°	-68.20°	Non
Reflex	135.00	5.20°	-68.10°	Non
Reflex	138.00	5.50°	-68.30°	Non
Reflex	141.00	5.40°	-68.10°	Non
Reflex	144.00	2.90°	-68.10°	Non
Reflex	147.00	5.10°	-67.50°	Non
Reflex	150.00	5.50°	-68.20°	Non
Reflex	153.00	5.60°	-68.30°	Non
Reflex	156.00	5.60°	-68.20°	Non
Reflex	159.00	5.60°	-68.20°	Non
Reflex	162.00	5.50°	-68.20°	Non
Reflex	165.00	5.70°	-68.20°	Non
Reflex	168.00	5.70°	-68.20°	Non
Reflex	171.00	5.80°	-68.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	174.00	6.10°	-68.20°	Non
Reflex	177.00	6.10°	-68.20°	Non
Reflex	180.00	5.90°	-68.20°	Non
Reflex	183.00	6.30°	-68.20°	Non
Reflex	186.00	6.90°	-68.20°	Non
Reflex	189.00	6.30°	-68.20°	Non
Reflex	192.00	6.40°	-68.20°	Non
Reflex	195.00	6.30°	-68.20°	Non
Reflex	198.00	6.60°	-68.20°	Non
Reflex	201.00	6.70°	-68.30°	Non
Reflex	204.00	6.50°	-68.20°	Non
Reflex	207.00	6.50°	-68.20°	Non
Reflex	210.00	6.60°	-68.10°	Non
Reflex	213.00	6.50°	-68.10°	Non
Reflex	216.00	6.40°	-68.10°	Non
Reflex	219.00	6.80°	-68.00°	Non
Reflex	222.00	6.90°	-68.00°	Non
Reflex	225.00	6.90°	-68.00°	Non
Reflex	228.00	6.80°	-68.00°	Non
Reflex	231.00	6.80°	-68.00°	Non
Reflex	234.00	7.10°	-68.00°	Non
Reflex	237.00	6.90°	-67.90°	Non
Reflex	240.00	6.90°	-68.00°	Non
Reflex	243.00	6.90°	-68.00°	Non
Reflex	246.00	7.50°	-68.00°	Non
Reflex	249.00	7.40°	-67.80°	Non
Reflex	252.00	7.40°	-68.00°	Non
Reflex	255.00	7.60°	-68.00°	Non
Reflex	258.00	7.90°	-68.00°	Non
Reflex	261.00	8.40°	-68.00°	Oui
Reflex	264.00	7.70°	-68.00°	Non
Reflex	267.00	7.80°	-68.00°	Non
Reflex	270.00	8.10°	-68.00°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	8.00°	-68.00°	Non	Reflex	372.00	9.60°	-68.30°	Non
Reflex	276.00	7.70°	-67.90°	Non	Reflex	375.00	9.30°	-68.20°	Non
Reflex	279.00	8.00°	-68.00°	Non	Reflex	378.00	9.30°	-68.30°	Non
Reflex	282.00	8.20°	-68.10°	Non	Reflex	381.00	9.50°	-68.30°	Non
Reflex	285.00	8.30°	-68.00°	Non	Reflex	384.00	9.50°	-68.30°	Non
Reflex	288.00	8.20°	-68.10°	Non	Reflex	387.00	9.70°	-68.30°	Non
Reflex	291.00	8.10°	-68.00°	Non	Reflex	390.00	9.80°	-68.30°	Non
Reflex	294.00	7.90°	-68.10°	Non	Reflex	393.00	9.00°	-68.30°	Non
Reflex	297.00	8.20°	-68.10°	Non	Reflex	396.00	9.50°	-68.30°	Non
Reflex	300.00	8.30°	-68.10°	Non	Reflex	399.00	9.60°	-68.40°	Non
Reflex	303.00	8.40°	-68.10°	Non	Reflex	402.00	9.60°	-68.40°	Non
Reflex	306.00	8.00°	-68.20°	Non	Reflex	405.00	9.70°	-68.30°	Non
Reflex	309.00	8.60°	-68.20°	Non	Reflex	408.00	9.90°	-68.40°	Non
Reflex	312.00	8.30°	-68.00°	Non	Reflex	411.00	9.50°	-68.40°	Non
Reflex	315.00	8.50°	-68.20°	Non	Reflex	414.00	10.00°	-68.40°	Non
Reflex	318.00	8.20°	-68.20°	Non	Reflex	417.00	9.60°	-68.40°	Non
Reflex	321.00	8.60°	-68.20°	Non	Reflex	420.00	9.60°	-68.40°	Non
Reflex	324.00	8.20°	-68.20°	Non	Reflex	423.00	9.60°	-68.40°	Non
Reflex	327.00	8.80°	-68.20°	Non	Reflex	426.00	9.30°	-68.40°	Non
Reflex	330.00	8.70°	-68.10°	Non	Reflex	429.00	9.30°	-68.40°	Non
Reflex	333.00	9.20°	-68.20°	Non	Reflex	432.00	9.40°	-68.40°	Non
Reflex	336.00	8.70°	-68.20°	Non	Reflex	435.00	9.60°	-68.40°	Non
Reflex	339.00	9.20°	-68.20°	Non	Reflex	438.00	9.60°	-68.40°	Non
Reflex	342.00	8.60°	-68.10°	Non	Reflex	441.00	9.60°	-68.30°	Non
Reflex	345.00	10.00°	-68.30°	Non					
Reflex	348.00	9.70°	-68.30°	Non					
Reflex	351.00	9.20°	-68.30°	Non					
Reflex	354.00	9.40°	-68.20°	Non					
Reflex	357.00	9.70°	-68.20°	Non					
Reflex	360.00	9.00°	-68.30°	Non					
Reflex	363.00	9.10°	-68.30°	Non					
Reflex	366.00	8.90°	-68.30°	Non					
Reflex	369.00	9.00°	-68.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT <b>Mort-terrain</b>						
2.20	16.00	SY; POR; FIN <b>Syénite; Porphyrique; Grains fins</b> Syénite à grains fins et porphyrique avec phénocristaux Xmm à Xcm.	2.20	3.50	D006779	1.30	0.041	0.041
			3.50	5.00	D006780	1.50	0.006	0.006
			5.00	6.50	D006781	1.50	0.020	0.020
			6.50	8.00	D006783	1.50	0.124	0.124
			8.00	9.50	D006784	1.50	1.380	1.380
			9.50	11.00	D006785	1.50	0.386	0.386
			11.00	12.50	D006786	1.50	0.020	0.020
			12.50	14.00	D006788	1.50	0.011	0.011
			14.00	15.00	D006789	1.00	0.011	0.011
			15.00	16.00	D006790	1.00	0.008	0.008
16.00	24.50	BA; MAS; COU <b>Basalte andésitique 55°; Roche massive; Coussiné</b> Basalte andésitique, massive avec de passage coussiné et rare amugdules.	16.00	17.50	D006791	1.50	0.119	0.119
			17.50	19.00	D006792	1.50	0.009	0.009
			19.00	20.50	D006793	1.50	0.025	0.025
			20.50	22.00	D006794	1.50	0.025	0.025
			22.00	23.00	D006795	1.00	0.172	0.172
			23.00	24.50	D006796	1.50	0.006	0.006
24.50	57.50	SY; POR; FIN <b>Syénite 45°; Porphyrique; Grains fins</b> Syénite à grains fins et porphyrique avec de phénocristaux Xmm à Xcm.	24.50	26.00	D006798	1.50	0.324	0.324
			26.00	27.50	D006799	1.50	2.180	2.180
			27.50	29.00	D006800	1.50	1.835	1.835
			29.00	30.50	D006801	1.50	0.333	0.333
			30.50	32.00	D006802	1.50	0.663	0.663
			32.00	33.50	D006803	1.50	0.289	0.289
			33.50	35.00	D006804	1.50	0.054	0.054
			35.00	36.50	D006805	1.50	1.400	1.400
			36.50	38.00	D006806	1.50	0.479	0.479
			38.00	39.50	D006808	1.50	0.082	0.082
			39.50	41.00	D006809	1.50	0.114	0.114
			41.00	42.50	D006810	1.50	0.097	0.097
			42.50	44.00	D006811	1.50	0.250	0.250
			44.00	45.50	D006812	1.50	0.023	0.023
			45.50	47.00	D006813	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
57.50	71.40	BA; MAS; COU; FIN <b>Basalte andésitique 55°; Roche massive; Coussiné; Grains fins</b> Basalte andésitique, massive, à grains fins, avec de passage coussiné et qlq rare amugdules.	47.00	48.50	D006814	1.50	0.019		0.019
			48.50	50.00	D006815	1.50	0.013		0.013
			50.00	51.00	D006816	1.00	0.022		0.022
			51.00	52.50	D006818	1.50	0.009		0.009
			52.50	54.00	D006819	1.50	0.009		0.009
			54.00	55.50	D006820	1.50	0.015		0.015
			55.50	56.50	D006821	1.00	0.011		0.011
			56.50	57.50	D006823	1.00	0.207		0.207
			57.50	59.00	D006824	1.50	0.536		0.536
			59.00	60.50	D006825	1.50	0.008		0.008
			60.50	62.00	D006826	1.50	0.005		0.005
			62.00	63.50	D006828	1.50	0.005		0.005
			63.50	65.00	D006829	1.50	<0.005		0.001
			65.00	66.50	D006830	1.50	<0.005		0.001
			66.50	68.00	D006831	1.50	0.009		0.009
			68.00	69.00	D006832	1.00	0.011		0.011
			69.00	70.00	D006833	1.00	0.011		0.011
70.00	71.40	D006834	1.40	0.032		0.032			
71.40	99.00	SY; FIN <b>Syénite; Grains fins</b> Syénite à grains fins, passage de qlq VCB et rarement VQZ.	71.40	73.00	D006835	1.60	0.664		0.664
			73.00	74.50	D006836	1.50	0.212		0.212
			74.50	76.00	D006838	1.50	0.049		0.049
			76.00	77.50	D006839	1.50	0.043		0.043
			77.50	79.00	D006840	1.50	0.041		0.041
			79.00	80.50	D006841	1.50	0.055		0.055
			80.50	82.00	D006842	1.50	0.018		0.018
			82.00	83.50	D006843	1.50	0.288		0.288
			83.50	85.00	D006844	1.50	0.025		0.025
			85.00	86.50	D006845	1.50	0.029		0.029
			86.50	88.00	D006846	1.50	0.051		0.051
			88.00	89.50	D006848	1.50	1.200		1.200
			89.50	91.00	D006849	1.50	0.020		0.020
			91.00	92.50	D006850	1.50	0.037		0.037
			92.50	94.00	D006851	1.50	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
99.00	104.30	BA; MAS; FIN; COU <b>Basalte 55°; Roche massive; Grains fins; Coussiné</b> Basalte, massive, à grains fins, avec de passage cousiné et qlq rare amugdules.	94.00	95.50	D006852	1.50	0.060		0.060			
			95.50	97.00	D006853	1.50	0.051		0.051			
			97.00	98.00	D006854	1.00	0.010		0.010			
			98.00	99.00	D006855	1.00	0.060		0.060			
			99.00	100.50	D006856	1.50	0.042		0.042			
			100.50	102.00	D006858	1.50	<0.005		0.001			
			102.00	103.00	D006859	1.00	0.005		0.005			
			103.00	104.30	D006860	1.30	0.009		0.009			
			104.30	137.40	TU; FIN <b>Tuf felsique; Grains fins</b> Tuf à cendre felsique avec de passage cisailé.	104.30	105.50	D006861	1.20	0.331		0.331
						105.50	107.00	D006863	1.50	0.075		0.075
107.00	108.50	D006864				1.50	<0.005		0.001			
108.50	110.00	D006865				1.50	<0.005		0.001			
110.00	111.50	D006866				1.50	0.008		0.008			
111.50	113.00	D006868				1.50	0.454		0.454			
113.00	114.50	D006869				1.50	0.016		0.016			
114.50	116.00	D006870				1.50	<0.005		0.001			
116.00	117.50	D006871				1.50	0.038		0.038			
117.50	119.00	D006872				1.50	0.146		0.146			
119.00	120.50	D006873				1.50	0.583		0.583			
120.50	122.00	D006874				1.50	0.026		0.026			
122.00	123.50	D006875				1.50	0.007		0.007			
123.50	125.00	D006876				1.50	0.017		0.017			
125.00	126.50	D006878				1.50	0.168		0.168			
126.50	128.00	D006879				1.50	0.070		0.070			
128.00	129.50	D006880				1.50	<0.005		0.001			
129.50	131.00	D006881				1.50	0.006		0.006			
131.00	132.50	D006882				1.50	<0.005		0.001			
132.50	134.00	D006883	1.50	<0.005		0.001						
134.00	135.00	D006884	1.00	<0.005		0.001						
135.00	136.00	D006885	1.00	<0.005		0.001						
136.00	137.40	D006886	1.40	<0.005		0.001						
137.40	194.00	SY; FIN <b>Syénite 65°; Grains fins</b> Syénite à grains fins avec passage de qlq VCB.	137.40	139.00	D006888	1.60	1.005		1.005			
			139.00	140.50	D006889	1.50	0.151		0.151			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	140.50	142.00	D006890	1.50	<0.005		0.001
	142.00	143.50	D006891	1.50	0.005		0.005
	143.50	145.00	D006892	1.50	0.013		0.013
	145.00	146.50	D006893	1.50	0.070		0.070
	146.50	148.00	D006894	1.50	0.050		0.050
	148.00	149.50	D006895	1.50	0.220		0.220
	149.50	151.00	D006896	1.50	0.595		0.595
	151.00	152.50	D006898	1.50	0.345		0.345
	152.50	154.00	D006899	1.50	<0.005		0.001
	154.00	155.50	D006900	1.50	<0.005		0.001
	155.50	157.00	D006901	1.50	<0.005		0.001
	157.00	158.50	D006903	1.50	<0.005		0.001
	158.50	160.00	D006904	1.50	0.008		0.008
	160.00	161.50	D006905	1.50	<0.005		0.001
	161.50	163.00	D006906	1.50	0.087		0.087
	163.00	164.50	D006908	1.50	<0.005		0.001
	164.50	166.00	D006909	1.50	0.414		0.414
	166.00	167.50	D006910	1.50	0.025		0.025
	167.50	169.00	D006911	1.50	0.005		0.005
	169.00	170.50	D006912	1.50	<0.005		0.001
	170.50	172.00	D006913	1.50	0.007		0.007
	172.00	173.50	D006914	1.50	0.049		0.049
	173.50	175.00	D006915	1.50	0.123		0.123
	175.00	176.50	D006916	1.50	2.020		2.020
	176.50	178.00	D006918	1.50	0.029		0.029
	178.00	179.50	D006919	1.50	0.016		0.016
	179.50	181.00	D006920	1.50	0.059		0.059
	181.00	182.50	D006921	1.50	0.782		0.782
	182.50	184.00	D006922	1.50	<0.005		0.001
	184.00	185.50	D006923	1.50	0.008		0.008
	185.50	187.00	D006924	1.50	<0.005		0.001
	187.00	188.50	D006925	1.50	0.005		0.005
	188.50	190.00	D006926	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
194.00	227.30	BA; FIN; COU <b>Basalte andésitique; Grains fins; Coussiné</b> Basalte andésitique à grains fins, cousiné avec VQZ au bordure de certains.	190.00	191.50	D006928	1.50	0.016		0.016
			191.50	193.00	D006929	1.50	1.565		1.565
			193.00	194.00	D006930	1.00	1.610		1.610
			194.00	195.50	D006931	1.50	0.013		0.013
			195.50	197.00	D006932	1.50	<0.005		0.001
			197.00	198.50	D006933	1.50	<0.005		0.001
			198.50	200.00	D006934	1.50	<0.005		0.001
			200.00	201.50	D006935	1.50	<0.005		0.001
			201.50	203.00	D006936	1.50	0.005		0.005
			203.00	204.50	D006938	1.50	<0.005		0.001
			204.50	206.00	D006939	1.50	<0.005		0.001
			206.00	207.50	D006940	1.50	<0.005		0.001
			207.50	209.00	D006941	1.50	<0.005		0.001
			209.00	210.50	D006943	1.50	<0.005		0.001
			210.50	212.00	D006944	1.50	0.005		0.005
			212.00	213.50	D006945	1.50	<0.005		0.001
			213.50	215.00	D006946	1.50	0.006		0.006
			215.00	216.50	D006947	1.50	<0.005		0.001
			216.50	218.00	D006948	1.50	<0.005		0.001
			218.00	219.50	D006949	1.50	0.010		0.010
219.50	221.00	D006950	1.50	0.009		0.009			
221.00	222.50	D006951	1.50	<0.005		0.001			
222.50	224.00	D006952	1.50	<0.005		0.001			
224.00	225.00	D006953	1.00	<0.005		0.001			
225.00	226.00	D006954	1.00	0.012		0.012			
226.00	227.30	D006955	1.30	0.043		0.043			
227.30	335.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique à phénocristaux Xmm à Xcm , sub-arrondi à allongé.	227.30	228.50	D006956	1.20	1.120		1.120
			228.50	230.00	D006958	1.50	0.646		0.646
			230.00	231.50	D006959	1.50	0.072		0.072
			231.50	233.00	D006960	1.50	0.083		0.083
			233.00	234.50	D006961	1.50	0.092		0.092
			234.50	236.00	D006962	1.50	0.028		0.028
			236.00	237.50	D006963	1.50	0.204		0.204

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	237.50	239.00	D006964	1.50	0.162		0.162
	239.00	240.50	D006965	1.50	0.027		0.027
	240.50	242.00	D006966	1.50	0.351		0.351
	242.00	243.50	D006968	1.50	0.068		0.068
	243.50	245.00	D006969	1.50	0.386		0.386
	245.00	246.50	D006970	1.50	0.321		0.321
	246.50	248.00	D006971	1.50	0.064		0.064
	248.00	249.50	D006972	1.50	0.030		0.030
	249.50	251.00	D006973	1.50	0.556		0.556
	251.00	252.50	D006974	1.50	0.012		0.012
	252.50	254.00	D006975	1.50	0.005		0.005
	254.00	255.50	D006976	1.50	<0.005		0.001
	255.50	257.00	D006978	1.50	0.134		0.134
	257.00	258.50	D006979	1.50	0.009		0.009
	258.50	260.00	D006980	1.50	<0.005		0.001
	260.00	261.50	D006981	1.50	<0.005		0.001
	261.50	263.00	D006983	1.50	<0.005		0.001
	263.00	264.50	D006984	1.50	0.008		0.008
	264.50	266.00	D006985	1.50	0.006		0.006
	266.00	267.50	D006986	1.50	<0.005		0.001
	267.50	269.00	D006988	1.50	<0.005		0.001
	269.00	270.50	D006989	1.50	0.010		0.010
	270.50	272.00	D006990	1.50	<0.005		0.001
	272.00	273.50	D006991	1.50	<0.005		0.001
	273.50	275.00	D006992	1.50	<0.005		0.001
	275.00	276.50	D006993	1.50	<0.005		0.001
	276.50	278.00	D006994	1.50	<0.005		0.001
	278.00	279.50	D006995	1.50	<0.005		0.001
	279.50	281.00	D006996	1.50	<0.005		0.001
	281.00	282.50	D006998	1.50	0.017		0.017
	282.50	284.00	D006999	1.50	0.035		0.035
	284.00	285.50	D007000	1.50	0.012		0.012
	285.50	287.00	D007001	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	287.00	288.50	D007002	1.50	<0.005		0.001
	288.50	290.00	D007003	1.50	0.038		0.038
	290.00	291.50	D007004	1.50	0.005		0.005
	291.50	293.00	D007005	1.50	0.022		0.022
	293.00	294.50	D007006	1.50	0.008		0.008
	294.50	296.00	D007008	1.50	0.022		0.022
	296.00	297.50	D007009	1.50	0.044		0.044
	297.50	299.00	D007010	1.50	0.431		0.431
	299.00	300.50	D007011	1.50	<0.005		0.001
	300.50	302.00	D007012	1.50	0.035		0.035
	302.00	303.50	D007013	1.50	0.018		0.018
	303.50	305.00	D007014	1.50	<0.005		0.001
	305.00	306.50	D007015	1.50	<0.005		0.001
	306.50	308.00	D007016	1.50	0.013		0.013
	308.00	309.50	D007018	1.50	0.010		0.010
	309.50	311.00	D007019	1.50	<0.005		0.001
	311.00	312.50	D007020	1.50	0.010		0.010
	312.50	314.00	D007021	1.50	<0.005		0.001
	314.00	315.50	D007023	1.50	<0.005		0.001
	315.50	317.00	D007024	1.50	<0.005		0.001
	317.00	318.50	D007025	1.50	<0.005		0.001
	318.50	320.00	D007026	1.50	<0.005		0.001
	320.00	321.50	D007028	1.50	<0.005		0.001
	321.50	323.00	D007029	1.50	<0.005		0.001
	323.00	324.50	D007030	1.50	<0.005		0.001
	324.50	326.00	D007031	1.50	<0.005		0.001
	326.00	327.50	D007032	1.50	<0.005		0.001
	327.50	329.00	D007033	1.50	<0.005		0.001
	329.00	330.50	D007034	1.50	<0.005		0.001
	330.50	332.00	D007035	1.50	0.005		0.005
	332.00	333.50	D007036	1.50	<0.005		0.001
	333.50	335.00	D007038	1.50	0.136		0.136
	335.00	336.50	D007039	1.50	0.074		0.074
335.00      352.00      SY; FIN; MAS Syénite; Grains fins; Roche massive							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Syénite , massive,à grains fins avec qlq VCB.			336.50	338.00	D007040	1.50	0.009		0.009
			338.00	339.50	D007041	1.50	0.024		0.024
			339.50	341.00	D007042	1.50	0.227		0.227
			341.00	342.50	D007043	1.50	<0.005		0.001
			342.50	344.00	D007044	1.50	0.493		0.493
			344.00	345.50	D007045	1.50	0.015		0.015
			345.50	347.00	D007046	1.50	<0.005		0.001
			347.00	348.50	D007048	1.50	<0.005		0.001
			348.50	350.00	D007049	1.50	<0.005		0.001
			350.00	351.00	D007050	1.00	<0.005		0.001
			351.00	352.00	D007051	1.00	0.478		0.478
			352.00	353.50	D007052	1.50	0.578		0.578
			353.50	355.00	D007053	1.50	0.051		0.051
			355.00	356.50	D007054	1.50	0.007		0.007
			356.50	358.00	D007055	1.50	<0.005		0.001
			358.00	359.50	D007056	1.50	0.010		0.010
			359.50	361.00	D007058	1.50	<0.005		0.001
361.00	362.50	D007059	1.50	0.025		0.025			
362.50	364.00	D007060	1.50	0.358		0.358			
364.00	365.50	D007061	1.50	0.108		0.108			
365.50	367.00	D007063	1.50	0.063		0.063			
367.00	368.50	D007064	1.50	0.080		0.080			
368.50	370.00	D007065	1.50	0.071		0.071			
370.00	371.50	D007066	1.50	0.073		0.073			
371.50	373.00	D007068	1.50	0.060		0.060			
373.00	374.50	D007069	1.50	0.288		0.288			
374.50	376.00	D007070	1.50	0.110		0.110			
376.00	377.50	D007071	1.50	0.081		0.081			
377.50	379.00	D007072	1.50	0.033		0.033			
379.00	380.50	D007073	1.50	0.153		0.153			
380.50	382.00	D007074	1.50	0.047		0.047			
382.00	383.50	D007075	1.50	0.147		0.147			
383.50	385.00	D007076	1.50	0.058		0.058			
352.00	441.00	SY; POR; FIN <b>Syénite; Porphyrique; Grains fins</b> Syénite porphyrique avec des phénocristaux Xmm à rarement Xcm, qlq VCB et qlq passage MG+.							

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	385.00	386.50	D007078	1.50	0.033		0.033
	386.50	388.00	D007079	1.50	0.186		0.186
	388.00	389.50	D007080	1.50	0.337		0.337
	389.50	391.00	D007081	1.50	0.164		0.164
	391.00	392.50	D007082	1.50	0.438		0.438
	392.50	394.00	D007083	1.50	0.094		0.094
	394.00	395.50	D007084	1.50	<0.005		0.001
	395.50	397.00	D007085	1.50	0.153		0.153
	397.00	398.50	D007086	1.50	0.302		0.302
	398.50	400.00	D007088	1.50	0.085		0.085
	400.00	401.50	D007089	1.50	0.182		0.182
	401.50	403.00	D007090	1.50	0.620		0.620
	403.00	404.50	D007091	1.50	0.103		0.103
	404.50	406.00	D007092	1.50	<0.005		0.001
	406.00	407.50	D007093	1.50	<0.005		0.001
	407.50	409.00	D007094	1.50	0.005		0.005
	409.00	410.50	D007095	1.50	1.270		1.270
	410.50	412.00	D007096	1.50	4.510	4.56	4.560
	412.00	413.50	D007098	1.50	2.590		2.590
	413.50	415.00	D007099	1.50	0.497		0.497
	415.00	416.50	D007100	1.50	0.082		0.082
	416.50	418.00	D007101	1.50	0.087		0.087
	418.00	419.50	D007103	1.50	0.064		0.064
	419.50	421.00	D007104	1.50	0.146		0.146
	421.00	422.50	D007105	1.50	0.214		0.214
	422.50	424.00	D007106	1.50	0.384		0.384
	424.00	425.50	D007108	1.50	0.397		0.397
	425.50	427.00	D007109	1.50	0.080		0.080
	427.00	428.50	D007110	1.50	0.257		0.257
	428.50	430.00	D007111	1.50	<0.005		0.001
	430.00	431.50	D007112	1.50	<0.005		0.001
	431.50	433.00	D007113	1.50	<0.005		0.001
	433.00	434.50	D007114	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	434.50	436.00	D007115	1.50	0.008		0.008
	436.00	437.50	D007116	1.50	0.130		0.130
	437.50	439.00	D007118	1.50	<0.005		0.001
	439.00	440.00	D007119	1.00	<0.005		0.001
	440.00	441.00	D007120	1.00	<0.005		0.001
441.00	Fin du sondage Nombre d'échantillons : 300 Nombre d'échantillons QAQC : 42 Longueur totale échantillonnée : 438.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.00	6.50	D006782	M1	1.50	<0.005	0.001
11.00	12.50	D006787	F2	1.50	8.550	8.550
23.00	24.50	D006797	D006796	1.50	<0.005	0.001
36.50	38.00	D006807	H	1.50	0.945	0.945
50.00	51.00	D006817	D006816	1.00	0.019	0.019
55.50	56.50	D006822	M1	1.00	<0.005	0.001
60.50	62.00	D006827	D2	1.50	0.828	0.828
73.00	74.50	D006837	D006836	1.50	0.200	0.200
86.50	88.00	D006847	A3	1.50	0.592	0.592
99.00	100.50	D006857	D006856	1.50	0.038	0.038
104.30	105.50	D006862	M1	1.20	<0.005	0.001
110.00	111.50	D006867	G2	1.50	3.890	3.940
123.50	125.00	D006877	D006876	1.50	0.018	0.018
136.00	137.40	D006887	C4	1.40	1.285	1.285
149.50	151.00	D006897	D006896	1.50	0.744	0.744
155.50	157.00	D006902	M1	1.50	<0.005	0.001
161.50	163.00	D006907	D2	1.50	0.801	0.801
175.00	176.50	D006917	D006916	1.50	2.270	2.270
188.50	190.00	D006927	F2	1.50	8.520	8.360
201.50	203.00	D006937	D006936	1.50	<0.005	0.001
207.50	209.00	D006942	M1	1.50	<0.005	0.001
227.30	228.50	D006957	D006956	1.20	1.100	1.100
240.50	242.00	D006967	H	1.50	0.995	0.995
254.00	255.50	D006977	D006976	1.50	<0.005	0.001
260.00	261.50	D006982	M1	1.50	<0.005	0.001
266.00	267.50	D006987	A3	1.50	0.630	0.630
279.50	281.00	D006997	D006996	1.50	<0.005	0.001
293.00	294.50	D007007	B4	1.50	2.480	2.480
306.50	308.00	D007017	D007016	1.50	0.015	0.015
312.50	314.00	D007022	M1	1.50	<0.005	0.001
318.50	320.00	D007027	C4	1.50	1.280	1.280
332.00	333.50	D007037	D007036	1.50	<0.005	0.001
345.50	347.00	D007047	D2	1.50	0.848	0.848

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
358.00	359.50	D007057	D007056	1.50	<0.005	0.001
364.00	365.50	D007062	M1	1.50	<0.005	0.001
370.00	371.50	D007067	F2	1.50	8.390	8.530
383.50	385.00	D007077	D007076	1.50	0.022	0.022
397.00	398.50	D007087	G2	1.50	3.980	4.030
410.50	412.00	D007097	D007096	1.50	2.300	2.300
416.50	418.00	D007102	M1	1.50	<0.005	0.001
422.50	424.00	D007107	H	1.50	0.967	0.967
436.00	437.50	D007117	D007116	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-153**

Titre minier :

Section :                      630 800

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :

Décrit par :          David RUHARA

Lot :

Du :                      2010-03-28

Date de description :      2010-04-29

Au :                      2010-04-02

Collet

UTM

Azimut :                1.00°

Plongée :              -60.00°

Longueur :            482.00 m

Est                      630 793.5

Nord                    5 374 402.3

Élévation              313.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	6.40°	-60.20°	Oui
Reflex	5.00	357.80°	-60.10°	Oui
Reflex	8.00	358.80°	-59.90°	Non
Reflex	11.00	359.10°	-60.20°	Non
Reflex	14.00	359.30°	-59.60°	Non
Reflex	17.00	359.70°	-59.60°	Non
Reflex	20.00	360.00°	-59.70°	Non
Reflex	23.00	0.30°	-59.70°	Non
Reflex	26.00	359.70°	-59.70°	Non
Reflex	29.00	0.30°	-59.70°	Non
Reflex	32.00	0.10°	-59.70°	Non
Reflex	35.00	0.30°	-59.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.80°	-59.70°	Non
Reflex	41.00	1.00°	-59.70°	Non
Reflex	44.00	0.40°	-59.60°	Non
Reflex	47.00	0.60°	-59.70°	Non
Reflex	50.00	358.40°	-59.70°	Non
Reflex	53.00	0.30°	-59.70°	Non
Reflex	56.00	2.00°	-59.80°	Non
Reflex	59.00	2.90°	-59.80°	Non
Reflex	62.00	3.20°	-59.80°	Non
Reflex	65.00	3.20°	-59.70°	Non
Reflex	68.00	7.60°	-59.60°	Oui
Reflex	71.00	3.00°	-59.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.00°	-59.50°	Non	Reflex	173.00	1.50°	-58.90°	Non
Reflex	77.00	2.00°	-59.40°	Non	Reflex	176.00	0.90°	-58.80°	Non
Reflex	80.00	1.00°	-59.40°	Non	Reflex	179.00	1.40°	-58.90°	Non
Reflex	83.00	2.10°	-59.30°	Non	Reflex	182.00	2.50°	-58.90°	Non
Reflex	86.00	2.00°	-59.30°	Non	Reflex	185.00	3.10°	-58.90°	Non
Reflex	89.00	1.50°	-59.40°	Non	Reflex	188.00	4.60°	-59.10°	Non
Reflex	92.00	1.50°	-59.30°	Non	Reflex	191.00	5.20°	-59.20°	Non
Reflex	95.00	1.70°	-59.30°	Non	Reflex	194.00	4.70°	-59.00°	Non
Reflex	98.00	2.30°	-59.30°	Non	Reflex	197.00	2.60°	-59.00°	Non
Reflex	101.00	2.00°	-59.30°	Non	Reflex	200.00	3.00°	-59.00°	Non
Reflex	104.00	1.70°	-59.30°	Non	Reflex	203.00	2.90°	-58.90°	Non
Reflex	107.00	1.80°	-59.30°	Non	Reflex	206.00	2.90°	-58.80°	Non
Reflex	110.00	2.30°	-59.30°	Non	Reflex	209.00	3.10°	-58.90°	Non
Reflex	113.00	2.60°	-59.40°	Non	Reflex	212.00	3.00°	-59.00°	Non
Reflex	116.00	2.20°	-59.40°	Non	Reflex	215.00	2.70°	-59.10°	Non
Reflex	119.00	2.70°	-59.30°	Non	Reflex	218.00	6.40°	-59.00°	Non
Reflex	122.00	2.60°	-59.30°	Non	Reflex	221.00	5.50°	-59.10°	Non
Reflex	125.00	2.80°	-59.30°	Non	Reflex	224.00	5.80°	-59.10°	Non
Reflex	128.00	3.10°	-59.40°	Non	Reflex	227.00	3.60°	-59.00°	Non
Reflex	131.00	2.40°	-59.40°	Non	Reflex	230.00	3.80°	-59.00°	Non
Reflex	134.00	2.00°	-59.40°	Non	Reflex	233.00	3.60°	-59.00°	Non
Reflex	137.00	1.60°	-59.40°	Oui	Reflex	236.00	3.50°	-58.80°	Non
Reflex	140.00	2.10°	-59.60°	Non	Reflex	239.00	3.50°	-58.90°	Non
Reflex	143.00	1.20°	-59.60°	Non	Reflex	242.00	3.50°	-58.90°	Non
Reflex	146.00	2.00°	-59.70°	Non	Reflex	245.00	3.60°	-58.80°	Non
Reflex	149.00	2.30°	-59.70°	Non	Reflex	248.00	3.60°	-58.90°	Non
Reflex	152.00	2.30°	-59.60°	Non	Reflex	251.00	3.50°	-58.90°	Non
Reflex	155.00	2.30°	-59.50°	Non	Reflex	254.00	3.50°	-58.90°	Non
Reflex	158.00	2.40°	-59.30°	Non	Reflex	257.00	3.70°	-59.00°	Non
Reflex	161.00	2.40°	-59.10°	Non	Reflex	260.00	4.00°	-59.10°	Non
Reflex	164.00	2.30°	-58.80°	Non	Reflex	263.00	4.30°	-59.10°	Non
Reflex	167.00	2.30°	-58.80°	Non	Reflex	266.00	5.00°	-59.50°	Non
Reflex	170.00	1.90°	-58.90°	Non	Reflex	269.00	5.40°	-59.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.40°	-59.60°	Non
Reflex	275.00	4.90°	-59.60°	Non
Reflex	278.00	7.80°	-59.60°	Non
Reflex	281.00	9.00°	-59.60°	Oui
Reflex	284.00	8.10°	-59.60°	Non
Reflex	287.00	7.00°	-59.60°	Oui
Reflex	290.00	9.20°	-59.60°	Non
Reflex	293.00	8.60°	-59.60°	Non
Reflex	296.00	8.20°	-59.60°	Non
Reflex	299.00	8.50°	-59.60°	Non
Reflex	302.00	8.20°	-59.70°	Non
Reflex	305.00	8.50°	-59.60°	Non
Reflex	308.00	9.60°	-59.60°	Non
Reflex	311.00	10.40°	-59.70°	Non
Reflex	314.00	9.20°	-59.70°	Non
Reflex	317.00	7.90°	-59.70°	Non
Reflex	320.00	7.90°	-59.70°	Non
Reflex	323.00	10.90°	-59.80°	Non
Reflex	326.00	9.50°	-59.80°	Oui
Reflex	329.00	10.50°	-59.80°	Non
Reflex	332.00	11.90°	-59.80°	Non
Reflex	335.00	11.40°	-59.70°	Non
Reflex	338.00	11.00°	-59.60°	Non
Reflex	341.00	13.10°	-59.50°	Oui
Reflex	344.00	11.20°	-59.40°	Non
Reflex	347.00	9.40°	-59.30°	Non
Reflex	350.00	8.30°	-59.20°	Non
Reflex	353.00	9.40°	-59.20°	Non
Reflex	356.00	9.40°	-59.30°	Non
Reflex	359.00	9.70°	-59.30°	Non
Reflex	362.00	9.70°	-59.20°	Non
Reflex	365.00	9.50°	-59.20°	Non
Reflex	368.00	9.40°	-59.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	9.40°	-59.10°	Non
Reflex	374.00	9.50°	-59.20°	Non
Reflex	377.00	9.50°	-59.20°	Non
Reflex	380.00	9.60°	-59.20°	Non
Reflex	383.00	9.80°	-59.10°	Non
Reflex	386.00	9.90°	-58.90°	Non
Reflex	389.00	10.00°	-58.90°	Non
Reflex	392.00	10.20°	-59.00°	Non
Reflex	395.00	10.30°	-59.00°	Non
Reflex	398.00	10.50°	-59.00°	Non
Reflex	401.00	10.70°	-58.90°	Non
Reflex	404.00	11.00°	-58.90°	Non
Reflex	407.00	11.20°	-58.80°	Non
Reflex	410.00	11.30°	-58.70°	Non
Reflex	413.00	11.20°	-58.50°	Non
Reflex	416.00	11.20°	-58.30°	Non
Reflex	419.00	11.30°	-58.30°	Non
Reflex	422.00	11.40°	-58.10°	Non
Reflex	425.00	11.50°	-58.00°	Non
Reflex	428.00	11.60°	-58.00°	Non
Reflex	431.00	11.70°	-57.90°	Non
Reflex	434.00	11.80°	-57.80°	Non
Reflex	437.00	11.80°	-57.80°	Non
Reflex	440.00	11.80°	-57.70°	Non
Reflex	443.00	11.90°	-57.60°	Non
Reflex	446.00	11.70°	-57.50°	Non
Reflex	449.00	11.80°	-57.30°	Non
Reflex	452.00	11.60°	-57.10°	Non
Reflex	455.00	11.90°	-57.00°	Non
Reflex	458.00	11.90°	-56.90°	Non
Reflex	461.00	11.80°	-56.80°	Non
Reflex	464.00	11.70°	-56.70°	Non
Reflex	467.00	11.80°	-56.60°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	12.00°	-56.50°	Non					
Reflex	473.00	12.30°	-56.40°	Non					
Reflex	476.00	12.40°	-56.30°	Non					
Reflex	479.00	13.10°	-56.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.80	MT						
		<b>Mort-terrain</b>						
1.80	115.50	SY; POR	1.80	3.00	D007486	1.20	<0.005	0.001
		<b>Syénite; Porphyrique</b>	3.00	4.50	D007488	1.50	<0.005	0.001
		Syénite porphyrique avec de phénocristaux Xmm à rarement Xcm.	4.50	6.00	D007489	1.50	<0.005	0.001
		Passage de VCB et rarement VQZ.	6.00	7.50	D007490	1.50	<0.005	0.001
			7.50	9.00	D007491	1.50	0.007	0.007
			9.00	10.50	D007492	1.50	0.041	0.041
			10.50	12.00	D007493	1.50	0.051	0.051
			12.00	13.50	D007494	1.50	0.163	0.163
			13.50	15.00	D007495	1.50	0.064	0.064
			15.00	16.50	D007496	1.50	<0.005	0.001
			16.50	18.00	D007498	1.50	0.389	0.389
			18.00	19.50	D007499	1.50	0.568	0.568
			19.50	21.00	D007500	1.50	0.649	0.649
			21.00	22.50	D007501	1.50	0.133	0.133
			22.50	24.00	D007502	1.50	0.013	0.013
			24.00	25.50	D007503	1.50	0.011	0.011
			25.50	27.00	D007504	1.50	0.048	0.048
			27.00	28.50	D007505	1.50	<0.005	0.001
			28.50	30.00	D007506	1.50	0.068	0.068
			30.00	31.50	D007508	1.50	0.039	0.039
			31.50	33.00	D007509	1.50	<0.005	0.001
			33.00	34.50	D007510	1.50	<0.005	0.001
			34.50	36.00	D007511	1.50	0.006	0.006
			36.00	37.50	D007512	1.50	0.023	0.023
			37.50	39.00	D007513	1.50	0.005	0.005
			39.00	40.50	D007514	1.50	0.074	0.074
			40.50	42.00	D007515	1.50	0.049	0.049
			42.00	43.30	D007516	1.30	<0.005	0.001
			43.30	45.00	D007518	1.70	0.014	0.014
			45.00	46.50	D007519	1.50	<0.005	0.001
			46.50	48.00	D007520	1.50	0.043	0.043
			48.00	49.50	D007521	1.50	0.075	0.075



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.50	51.00	D007523	1.50	0.102		0.102
	51.00	52.50	D007524	1.50	0.015		0.015
	52.50	54.00	D007525	1.50	0.125		0.125
	54.00	55.50	D007526	1.50	0.159		0.159
	55.50	57.00	D007528	1.50	0.057		0.057
	57.00	58.50	D007529	1.50	<0.005		0.001
	58.50	60.00	D007530	1.50	<0.005		0.001
	60.00	61.50	D007531	1.50	<0.005		0.001
	61.50	63.00	D007532	1.50	0.557		0.557
	63.00	64.50	D007533	1.50	0.007		0.007
	64.50	66.00	D007534	1.50	0.012		0.012
	66.00	67.50	D007535	1.50	0.005		0.005
	67.50	69.00	D007536	1.50	0.102		0.102
	69.00	70.50	D007538	1.50	<0.005		0.001
	70.50	72.00	D007539	1.50	0.071		0.071
	72.00	73.50	D007540	1.50	<0.005		0.001
	73.50	75.00	D007541	1.50	<0.005		0.001
	75.00	76.50	D007542	1.50	0.053		0.053
	76.50	78.00	D007543	1.50	0.006		0.006
	78.00	79.50	D007544	1.50	<0.005		0.001
	79.50	81.00	D007545	1.50	0.138		0.138
	81.00	82.50	D007546	1.50	<0.005		0.001
	82.50	84.00	D007548	1.50	0.012		0.012
	84.00	85.50	D007549	1.50	<0.005		0.001
	85.50	87.00	D007550	1.50	<0.005		0.001
	87.00	88.50	D007551	1.50	0.099		0.099
	88.50	90.00	D007552	1.50	0.005		0.005
	90.00	91.50	D007553	1.50	0.136		0.136
	91.50	93.00	D007554	1.50	<0.005		0.001
	93.00	94.50	D007555	1.50	<0.005		0.001
	94.50	96.00	D007556	1.50	<0.005		0.001
	96.00	97.50	D007558	1.50	<0.005		0.001
	97.50	99.00	D007559	1.50	0.064		0.064

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
115.50	442.90	SY; FIN; MTY <b>Syénite; Grains fins; Grains moyens</b> Syénite à grains fins à grains moyens, qlq rare fantômes de phénocristaux, altération différentielle et qlq VCB.	99.00	100.50	D007560	1.50	<0.005		0.001
			100.50	102.00	D007561	1.50	<0.005		0.001
			102.00	103.50	D007563	1.50	<0.005		0.001
			103.50	105.00	D007564	1.50	<0.005		0.001
			105.00	106.50	D007565	1.50	0.006		0.006
			106.50	108.00	D007566	1.50	<0.005		0.001
			108.00	109.50	D007568	1.50	<0.005		0.001
			109.50	111.00	D007569	1.50	0.009		0.009
			111.00	112.50	D007570	1.50	0.036		0.036
			112.50	114.00	D007571	1.50	0.047		0.047
			114.00	115.50	D007572	1.50	0.010		0.010
			115.50	117.00	D007573	1.50	0.034		0.034
			117.00	118.50	D007574	1.50	0.139		0.139
			118.50	120.00	D007575	1.50	<0.005		0.001
			120.00	121.50	D007576	1.50	0.025		0.025
			121.50	123.00	D007578	1.50	0.034		0.034
			123.00	124.00	D007579	1.00	0.008		0.008
			124.00	125.50	D007580	1.50	0.009		0.009
			125.50	127.00	D007581	1.50	0.066		0.066
			127.00	128.50	D007582	1.50	0.078		0.078
			128.50	130.00	D007583	1.50	0.027		0.027
			130.00	131.50	D007584	1.50	0.323		0.323
			131.50	133.00	D007585	1.50	0.050		0.050
			133.00	134.50	D007586	1.50	0.172		0.172
			134.50	136.00	D007588	1.50	<0.005		0.001
			136.00	137.50	D007589	1.50	<0.005		0.001
			137.50	139.00	D007590	1.50	0.010		0.010
139.00	140.50	D007591	1.50	0.006		0.006			
140.50	142.00	D007592	1.50	0.113		0.113			
142.00	143.50	D007593	1.50	<0.005		0.001			
143.50	145.00	D007594	1.50	<0.005		0.001			
145.00	146.50	D007595	1.50	<0.005		0.001			
146.50	148.00	D007596	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.00	149.50	D007598	1.50	<0.005		0.001
	149.50	151.00	D007599	1.50	<0.005		0.001
	151.00	152.50	D007600	1.50	<0.005		0.001
	152.50	154.00	D007601	1.50	0.034		0.034
	154.00	155.50	D007603	1.50	<0.005		0.001
	155.50	157.00	D007604	1.50	<0.005		0.001
	157.00	158.50	D007605	1.50	<0.005		0.001
	158.50	160.00	D007606	1.50	<0.005		0.001
	160.00	161.50	D007608	1.50	<0.005		0.001
	161.50	163.00	D007609	1.50	0.010		0.010
	163.00	164.50	D007610	1.50	0.035		0.035
	164.50	166.00	D007611	1.50	0.011		0.011
	166.00	167.50	D007612	1.50	0.024		0.024
	167.50	169.00	D007613	1.50	0.020		0.020
	169.00	170.50	D007614	1.50	<0.005		0.001
	170.50	172.00	D007615	1.50	<0.005		0.001
	172.00	173.00	D007616	1.00	<0.005		0.001
	173.00	174.00	D007618	1.00	<0.005		0.001
	174.00	175.50	D007619	1.50	0.012		0.012
	175.50	177.00	D007620	1.50	<0.005		0.001
	177.00	178.50	D007621	1.50	<0.005		0.001
	178.50	180.00	D007622	1.50	0.012		0.012
	180.00	181.50	D007623	1.50	0.008		0.008
	181.50	183.00	D007624	1.50	0.009		0.009
	183.00	184.50	D007625	1.50	0.008		0.008
	184.50	186.00	D007626	1.50	<0.005		0.001
	186.00	187.50	D007628	1.50	<0.005		0.001
	187.50	189.00	D007629	1.50	<0.005		0.001
	189.00	190.50	D007630	1.50	<0.005		0.001
	190.50	192.00	D007631	1.50	<0.005		0.001
	192.00	193.50	D007632	1.50	<0.005		0.001
	193.50	195.00	D007633	1.50	<0.005		0.001
	195.00	196.50	D007634	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	196.50	198.00	D007635	1.50	<0.005		0.001
	198.00	199.50	D007636	1.50	<0.005		0.001
	199.50	201.00	D007638	1.50	<0.005		0.001
	201.00	202.50	D007639	1.50	<0.005		0.001
	202.50	204.00	D007640	1.50	<0.005		0.001
	204.00	205.50	D007641	1.50	0.013		0.013
	205.50	207.00	D007643	1.50	0.008		0.008
	207.00	208.50	D007644	1.50	<0.005		0.001
	208.50	210.00	D007645	1.50	<0.005		0.001
	210.00	211.50	D007646	1.50	<0.005		0.001
	211.50	213.00	D007648	1.50	<0.005		0.001
	213.00	214.50	D007649	1.50	0.005		0.005
	214.50	215.50	D007650	1.00	0.005		0.005
	215.50	217.00	D007651	1.50	<0.005		0.001
	217.00	218.50	D007652	1.50	<0.005		0.001
	218.50	220.00	D007653	1.50	<0.005		0.001
	220.00	221.50	D007654	1.50	<0.005		0.001
	221.50	223.00	D007655	1.50	<0.005		0.001
	223.00	224.50	D007656	1.50	<0.005		0.001
	224.50	226.00	D007658	1.50	<0.005		0.001
	226.00	227.50	D007659	1.50	0.102		0.102
	227.50	229.00	D007660	1.50	0.006		0.006
	229.00	230.50	D007661	1.50	<0.005		0.001
	230.50	232.00	D007662	1.50	<0.005		0.001
	232.00	233.50	D007663	1.50	<0.005		0.001
	233.50	235.00	D007664	1.50	<0.005		0.001
	235.00	236.50	D007665	1.50	<0.005		0.001
	236.50	238.00	D007666	1.50	<0.005		0.001
	238.00	239.50	D007668	1.50	0.006		0.006
	239.50	241.00	D007669	1.50	<0.005		0.001
	241.00	242.50	D007670	1.50	0.024		0.024
	242.50	244.00	D007671	1.50	<0.005		0.001
	244.00	245.50	D007672	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	245.50	247.00	D007673	1.50	0.010		0.010
	247.00	248.50	D007674	1.50	0.031		0.031
	248.50	250.00	D007675	1.50	0.006		0.006
	250.00	251.50	D007676	1.50	0.019		0.019
	251.50	253.00	D007678	1.50	<0.005		0.001
	253.00	254.50	D007679	1.50	<0.005		0.001
	254.50	256.00	D007680	1.50	<0.005		0.001
	256.00	257.50	D007681	1.50	<0.005		0.001
	257.50	259.00	D007683	1.50	<0.005		0.001
	259.00	260.50	D007684	1.50	<0.005		0.001
	260.50	262.00	D007685	1.50	<0.005		0.001
	262.00	263.50	D007686	1.50	0.026		0.026
	263.50	265.00	D007688	1.50	<0.005		0.001
	265.00	266.50	D007689	1.50	0.069		0.069
	266.50	268.00	D007690	1.50	<0.005		0.001
	268.00	269.50	D007691	1.50	<0.005		0.001
	269.50	271.00	D007692	1.50	<0.005		0.001
	271.00	272.50	D007693	1.50	<0.005		0.001
	272.50	274.00	D007694	1.50	<0.005		0.001
	274.00	275.50	D007695	1.50	<0.005		0.001
	275.50	277.00	D007696	1.50	<0.005		0.001
	277.00	278.50	D007698	1.50	0.007		0.007
	278.50	280.00	D007699	1.50	<0.005		0.001
	280.00	281.50	D007700	1.50	<0.005		0.001
	281.50	283.00	D007701	1.50	<0.005		0.001
	283.00	284.50	D007702	1.50	<0.005		0.001
	284.50	286.00	D007703	1.50	<0.005		0.001
	286.00	287.50	D007704	1.50	<0.005		0.001
	287.50	289.00	D007705	1.50	<0.005		0.001
	289.00	290.50	D007706	1.50	0.005		0.005
	290.50	292.00	D007708	1.50	<0.005		0.001
	292.00	293.50	D007709	1.50	0.007		0.007
	293.50	295.00	D007710	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	295.00	296.50	D007711	1.50	<0.005		0.001
	296.50	298.00	D007712	1.50	<0.005		0.001
	298.00	299.50	D007713	1.50	0.007		0.007
	299.50	301.00	D007714	1.50	<0.005		0.001
	301.00	302.50	D007715	1.50	<0.005		0.001
	302.50	304.00	D007716	1.50	0.013		0.013
	304.00	305.50	D007718	1.50	<0.005		0.001
	305.50	307.00	D007719	1.50	<0.005		0.001
	307.00	308.50	D007720	1.50	<0.005		0.001
	308.50	310.00	D007721	1.50	0.014		0.014
	310.00	311.50	D007723	1.50	<0.005		0.001
	311.50	313.00	D007724	1.50	<0.005		0.001
	313.00	314.50	D007725	1.50	0.046		0.046
	314.50	316.00	D007726	1.50	0.009		0.009
	316.00	317.50	D007728	1.50	<0.005		0.001
	317.50	319.00	D007729	1.50	<0.005		0.001
	319.00	320.50	D007730	1.50	<0.005		0.001
	320.50	322.00	D007731	1.50	<0.005		0.001
	322.00	323.50	D007732	1.50	<0.005		0.001
	323.50	325.00	D007733	1.50	<0.005		0.001
	325.00	326.50	D007734	1.50	<0.005		0.001
	326.50	328.00	D007735	1.50	<0.005		0.001
	328.00	329.50	D007736	1.50	<0.005		0.001
	329.50	331.00	D007738	1.50	0.007		0.007
	331.00	332.50	D007739	1.50	<0.005		0.001
	332.50	334.00	D007740	1.50	0.010		0.010
	334.00	335.50	D007741	1.50	0.009		0.009
	335.50	337.00	D007742	1.50	0.008		0.008
	337.00	338.50	D007743	1.50	0.019		0.019
	338.50	340.00	D007744	1.50	0.029		0.029
	340.00	341.50	D007745	1.50	0.045		0.045
	341.50	343.00	D007746	1.50	0.054		0.054
	343.00	344.50	D007748	1.50	0.081		0.081

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	344.50	346.00	D007749	1.50	0.045		0.045
	346.00	347.50	D007750	1.50	0.016		0.016
	347.50	349.00	D007751	1.50	0.023		0.023
	349.00	350.50	D007752	1.50	0.071		0.071
	350.50	352.00	D007753	1.50	0.012		0.012
	352.00	353.50	D007754	1.50	0.005		0.005
	353.50	355.00	D007755	1.50	0.064		0.064
	355.00	356.50	D007756	1.50	0.021		0.021
	356.50	358.00	D007758	1.50	0.006		0.006
	358.00	359.50	D007759	1.50	0.033		0.033
	359.50	361.00	D007760	1.50	0.171		0.171
	361.00	362.50	D007761	1.50	0.050		0.050
	362.50	364.00	D007763	1.50	0.047		0.047
	364.00	365.50	D007764	1.50	0.023		0.023
	365.50	367.00	D007765	1.50	0.019		0.019
	367.00	368.50	D007766	1.50	0.007		0.007
	368.50	370.00	D007768	1.50	0.009		0.009
	370.00	371.50	D007769	1.50	0.143		0.143
	371.50	373.00	D007770	1.50	0.025		0.025
	373.00	374.50	D007771	1.50	0.046		0.046
	374.50	376.00	D007772	1.50	<0.005		0.001
	376.00	377.50	D007773	1.50	0.035		0.035
	377.50	379.00	D007774	1.50	<0.005		0.001
	379.00	380.00	D007775	1.00	0.036		0.036
	380.00	381.50	D007776	1.50	0.093		0.093
	381.50	383.00	D007778	1.50	0.259		0.259
	383.00	384.50	D007779	1.50	0.047		0.047
	384.50	386.00	D007780	1.50	0.005		0.005
	386.00	387.50	D007781	1.50	0.012		0.012
	387.50	389.00	D007782	1.50	0.005		0.005
	389.00	390.50	D007783	1.50	0.014		0.014
	390.50	392.00	D007784	1.50	0.007		0.007
	392.00	393.50	D007785	1.50	0.013		0.013

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	393.50	395.00	D007786	1.50	0.022		0.022
	395.00	396.50	D007788	1.50	0.047		0.047
	396.50	398.00	D007789	1.50	0.005		0.005
	398.00	399.50	D007790	1.50	0.005		0.005
	399.50	401.00	D007791	1.50	0.008		0.008
	401.00	402.50	D007792	1.50	<0.005		0.001
	402.50	404.00	D007793	1.50	0.010		0.010
	404.00	405.50	D007794	1.50	0.005		0.005
	405.50	407.00	D007795	1.50	0.007		0.007
	407.00	408.50	D007796	1.50	1.350		1.350
	408.50	410.00	D007798	1.50	1.130		1.130
	410.00	411.50	D007799	1.50	0.544		0.544
	411.50	413.00	D007800	1.50	0.008		0.008
	413.00	414.50	D007801	1.50	0.026		0.026
	414.50	416.00	D007803	1.50	0.243		0.243
	416.00	417.50	D007804	1.50	0.024		0.024
	417.50	419.00	D007805	1.50	1.100		1.100
	419.00	420.50	D007806	1.50	0.719		0.719
	420.50	422.00	D007808	1.50	0.785		0.785
	422.00	423.50	D007809	1.50	2.440		2.440
	423.50	425.00	D007810	1.50	3.050	2.93	2.930
	425.00	426.50	D007811	1.50	1.740		1.740
	426.50	428.00	D007812	1.50	0.890		0.890
	428.00	429.50	D007813	1.50	1.490		1.490
	429.50	431.00	D007814	1.50	2.090		2.090
	431.00	432.50	D007815	1.50	0.573		0.573
	432.50	434.00	D007816	1.50	2.490		2.490
	434.00	435.50	D007818	1.50	4.840	4.79	4.790
	435.50	437.00	D007819	1.50	0.471		0.471
	437.00	438.50	D007820	1.50	0.339		0.339
	438.50	440.00	D007821	1.50	0.116		0.116
	440.00	441.50	D007822	1.50	0.042		0.042
	441.50	442.90	D007823	1.40	0.154		0.154



Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
442.90	482.00	BA; AMY <b>Basalte 25°; Amygdalaire</b> Basalte massive à amygdalaire à altération différentielle avec qlq VCB.	442.90	444.50	D007824	1.60	<0.005		0.001		
			444.50	446.00	D007825	1.50	<0.005		0.001		
			446.00	447.50	D007826	1.50	0.147		0.147		
			447.50	449.00	D007828	1.50	0.125		0.125		
			449.00	450.50	D007829	1.50	0.776		0.776		
			450.50	452.00	D007830	1.50	0.008		0.008		
			452.00	453.50	D007831	1.50	0.116		0.116		
			453.50	455.00	D007832	1.50	0.330		0.330		
			455.00	456.50	D007833	1.50	1.270		1.270		
			456.50	458.00	D007834	1.50	0.006		0.006		
			458.00	459.50	D007835	1.50	<0.005		0.001		
			459.50	461.00	D007836	1.50	<0.005		0.001		
			461.00	462.50	D007838	1.50	<0.005		0.001		
			462.50	464.00	D007839	1.50	<0.005		0.001		
			464.00	465.50	D007840	1.50	<0.005		0.001		
			465.50	467.00	D007841	1.50	<0.005		0.001		
			467.00	468.50	D007843	1.50	<0.005		0.001		
			468.50	470.00	D007844	1.50	<0.005		0.001		
			470.00	471.50	D007845	1.50	<0.005		0.001		
			471.50	473.00	D007846	1.50	<0.005		0.001		
			473.00	474.50	D007848	1.50	<0.005		0.001		
			474.50	476.00	D007849	1.50	<0.005		0.001		
			476.00	477.50	D007850	1.50	<0.005		0.001		
			477.50	479.00	D007851	1.50	<0.005		0.001		
			479.00	480.50	D007852	1.50	<0.005		0.001		
			480.50	482.00	D007853	1.50	<0.005		0.001		
			482.00	Fin du sondage Nombre d'échantillons : 322 Nombre d'échantillons QAQC : 46 Longueur totale échantillonnée : 480.20							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
1.80	3.00	D007487	F2	1.20	8.440	7.970
15.00	16.50	D007497	D007496	1.50	<0.005	0.001
28.50	30.00	D007507	H	1.50	1.030	1.030
42.00	43.30	D007517	D007516	1.30	<0.005	0.001
48.00	49.50	D007522	M1	1.50	<0.005	0.001
54.00	55.50	D007527	D2	1.50	0.849	0.849
67.50	69.00	D007537	D007536	1.50	0.137	0.137
81.00	82.50	D007547	A3	1.50	0.469	0.469
94.50	96.00	D007557	D007556	1.50	<0.005	0.001
100.50	102.00	D007562	M1	1.50	<0.005	0.001
106.50	108.00	D007567	G2	1.50	3.940	3.990
120.00	121.50	D007577	D007575	1.50	0.019	0.019
133.00	134.50	D007587	C4	1.50	1.335	1.335
146.50	148.00	D007597	D007596	1.50	<0.005	0.001
152.50	154.00	D007602	M1	1.50	<0.005	0.001
158.50	160.00	D007607	D2	1.50	0.849	0.849
172.00	173.00	D007617	D007616	1.00	<0.005	0.001
184.50	186.00	D007627	F2	1.50	8.520	8.420
198.00	199.50	D007637	D007636	1.50	<0.005	0.001
204.00	205.50	D007642	M1	1.50	<0.005	0.001
210.00	211.50	D007647	G2	1.50	3.840	4.010
223.00	224.50	D007657	D007656	1.50	<0.005	0.001
236.50	238.00	D007667	H	1.50	0.964	0.964
250.00	251.50	D007677	D007676	1.50	0.024	0.024
256.00	257.50	D007682	M1	1.50	<0.005	0.001
262.00	263.50	D007687	A3	1.50	0.613	0.613
275.50	277.00	D007697	D007696	1.50	<0.005	0.001
289.00	290.50	D007707	B4	1.50	2.680	2.680
302.50	304.00	D007717	D007716	1.50	0.017	0.017
308.50	310.00	D007722	M1	1.50	<0.005	0.001
314.50	316.00	D007727	C4	1.50	1.365	1.365
328.00	329.50	D007737	D007736	1.50	<0.005	0.001
341.50	343.00	D007747	D2	1.50	0.871	0.871

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
355.00	356.50	D007757	D007756	1.50	0.017	0.017
361.00	362.50	D007762	M1	1.50	<0.005	0.001
367.00	368.50	D007767	F2	1.50	8.180	8.400
380.00	381.50	D007777	D007776	1.50	0.283	0.283
393.50	395.00	D007787	G2	1.50	3.990	4.140
407.00	408.50	D007797	D007796	1.50	1.495	1.495
413.00	414.50	D007802	M1	1.50	<0.005	0.001
419.00	420.50	D007807	H	1.50	0.967	0.967
432.50	434.00	D007817	D007816	1.50	2.510	2.510
446.00	447.50	D007827	A3	1.50	0.578	0.578
459.50	461.00	D007837	D007836	1.50	<0.005	0.001
465.50	467.00	D007842	M1	1.50	<0.005	0.001
471.50	473.00	D007847	G2	1.50	4.080	4.000

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-154**

Titre minier :

Section :                      630 000

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles.KAMAT

Lot :

Du :                              2010-04-02

Date de description :

Au :                              2010-04-06

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      347.00 m

Est	629 999.9
Nord	5 374 250.5
Élévation	282.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	340.00°	-59.40°	Oui
Reflex	5.00	150.40°	-59.40°	Oui
Reflex	8.00	209.90°	-59.30°	Oui
Reflex	11.00	9.00°	-59.30°	Oui
Reflex	14.00	351.50°	-59.20°	Oui
Reflex	17.00	343.20°	-59.10°	Oui
Reflex	20.00	343.60°	-59.10°	Oui
Reflex	23.00	347.00°	-59.10°	Oui
Reflex	26.00	337.80°	-59.20°	Oui
Reflex	29.00	339.10°	-59.30°	Oui
Reflex	32.00	352.00°	-49.00°	Oui
Reflex	35.00	357.30°	-59.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	354.10°	-49.10°	Oui
Reflex	41.00	356.90°	-59.30°	Non
Reflex	44.00	357.80°	-59.30°	Non
Reflex	47.00	357.10°	-59.80°	Non
Reflex	50.00	356.50°	-59.40°	Non
Reflex	53.00	359.20°	-60.50°	Oui
Reflex	56.00	356.40°	-59.40°	Non
Reflex	59.00	354.30°	-59.50°	Non
Reflex	62.00	2.90°	-66.30°	Oui
Reflex	65.00	355.70°	-59.30°	Non
Reflex	68.00	356.70°	-59.50°	Non
Reflex	71.00	355.90°	-59.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	356.90°	-59.70°	Non	Reflex	173.00	358.10°	-61.10°	Non
Reflex	77.00	357.60°	-59.70°	Non	Reflex	176.00	358.00°	-61.10°	Non
Reflex	80.00	357.10°	-58.90°	Non	Reflex	179.00	357.60°	-60.10°	Non
Reflex	83.00	357.70°	-59.70°	Non	Reflex	182.00	358.20°	-61.00°	Non
Reflex	86.00	359.40°	-59.60°	Oui	Reflex	185.00	358.10°	-61.10°	Non
Reflex	89.00	358.10°	-59.80°	Non	Reflex	188.00	357.90°	-60.90°	Non
Reflex	92.00	359.20°	-59.70°	Oui	Reflex	191.00	358.00°	-60.90°	Non
Reflex	95.00	357.10°	-59.60°	Non	Reflex	194.00	358.00°	-60.60°	Non
Reflex	98.00	358.00°	-59.50°	Non	Reflex	197.00	356.30°	-57.50°	Non
Reflex	101.00	359.00°	-59.70°	Non	Reflex	200.00	358.40°	-60.30°	Non
Reflex	104.00	357.50°	-59.80°	Oui	Reflex	203.00	358.60°	-60.40°	Non
Reflex	107.00	359.00°	-59.90°	Non	Reflex	206.00	358.20°	-60.20°	Non
Reflex	110.00	359.20°	-59.90°	Non	Reflex	209.00	358.20°	-60.40°	Non
Reflex	113.00	358.00°	-60.00°	Non	Reflex	212.00	357.90°	-60.30°	Non
Reflex	116.00	359.00°	-60.40°	Non	Reflex	215.00	358.00°	-60.40°	Non
Reflex	119.00	359.30°	-60.30°	Non	Reflex	218.00	358.00°	-60.40°	Non
Reflex	122.00	359.20°	-60.30°	Non	Reflex	221.00	358.20°	-60.40°	Non
Reflex	125.00	359.20°	-60.20°	Non	Reflex	224.00	358.30°	-60.60°	Non
Reflex	128.00	0.00°	-60.30°	Non	Reflex	227.00	358.30°	-60.80°	Non
Reflex	131.00	0.10°	-60.30°	Non	Reflex	230.00	358.60°	-61.00°	Non
Reflex	134.00	0.20°	-60.30°	Non	Reflex	233.00	358.40°	-60.60°	Non
Reflex	137.00	0.20°	-60.10°	Non	Reflex	236.00	358.30°	-60.70°	Non
Reflex	140.00	0.30°	-60.20°	Non	Reflex	239.00	358.20°	-60.60°	Non
Reflex	143.00	0.20°	-60.30°	Non	Reflex	242.00	358.00°	-60.50°	Non
Reflex	146.00	360.00°	-60.40°	Non	Reflex	245.00	358.20°	-60.60°	Non
Reflex	149.00	359.90°	-60.80°	Non	Reflex	248.00	358.20°	-60.60°	Non
Reflex	152.00	359.70°	-60.60°	Non	Reflex	251.00	358.10°	-60.70°	Non
Reflex	155.00	0.60°	-60.80°	Non	Reflex	254.00	358.10°	-60.70°	Non
Reflex	158.00	359.20°	-60.80°	Non	Reflex	257.00	358.20°	-60.60°	Non
Reflex	161.00	359.10°	-60.90°	Non	Reflex	260.00	358.30°	-60.60°	Non
Reflex	164.00	358.80°	-60.90°	Non	Reflex	263.00	358.20°	-60.60°	Non
Reflex	167.00	358.50°	-61.00°	Non	Reflex	266.00	358.10°	-60.60°	Non
Reflex	170.00	358.30°	-61.10°	Non	Reflex	269.00	357.90°	-60.50°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	358.10°	-60.50°	Non					
Reflex	275.00	358.10°	-60.40°	Non					
Reflex	278.00	0.30°	-60.50°	Oui					
Reflex	281.00	358.90°	-60.50°	Non					
Reflex	284.00	358.40°	-60.40°	Non					
Reflex	287.00	358.60°	-60.40°	Non					
Reflex	290.00	358.60°	-60.40°	Non					
Reflex	293.00	358.50°	-60.30°	Non					
Reflex	296.00	358.60°	-60.30°	Non					
Reflex	299.00	358.60°	-60.40°	Non					
Reflex	302.00	358.70°	-60.30°	Non					
Reflex	305.00	358.90°	-60.30°	Non					
Reflex	308.00	358.80°	-60.30°	Non					
Reflex	311.00	358.50°	-60.30°	Non					
Reflex	314.00	358.60°	-60.20°	Non					
Reflex	317.00	358.80°	-60.10°	Non					
Reflex	320.00	358.90°	-60.10°	Non					
Reflex	323.00	359.00°	-60.10°	Non					
Reflex	326.00	359.20°	-60.10°	Non					
Reflex	329.00	359.20°	-60.00°	Non					
Reflex	332.00	359.60°	-60.00°	Non					
Reflex	335.00	359.60°	-60.00°	Non					
Reflex	338.00	359.60°	-59.90°	Non					
Reflex	341.00	359.60°	-59.70°	Non					
Reflex	344.00	359.70°	-59.70°	Non					
Reflex	347.00	359.70°	-59.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	10.80	MT						
		<b>Mort-terrain</b>						
10.80	20.00	SY; MAS; FIN; MAG	10.80	12.50	D001917	1.70	<0.005	0.001
		<b>Syénite; Roche massive; Grains fins; Magnétique</b>	12.50	14.00	D001918	1.50	0.010	0.010
		localement altéré en calcite, qlq phénocristaux automorphe, sub bréchification, légèrement hématisé et chloritisé, lentilles de QZ carbonaté, PY fine irrég diss	14.00	15.50	D001919	1.50	0.026	0.026
			15.50	17.00	D001920	1.50	0.896	0.896
			17.00	18.50	D001921	1.50	2.180	2.180
			18.50	20.00	D001922	1.50	0.556	0.556
20.00	21.30	NR						
		<b>Carotte perdue</b>						
21.30	23.00	SY; MAS; FIN; MAG	21.30	23.00	D001923	1.70	<0.005	0.001
		<b>Syénite; Roche massive; Grains fins; Magnétique</b>						
		localement altéré en calcite, légèrement cataclasé, chloritisation et hématisation, veinules de calcite						
23.00	24.30	NR						
		<b>Carotte perdue</b>						
24.30	116.70	SY; MAS; MAG	24.30	25.50	D001924	1.20	<0.005	0.001
		<b>Syénite; Roche massive; Magnétique</b>	25.50	27.00	D001925	1.50	<0.005	0.001
		localement quelques phénocristaux, légèrement cataclasé, localement bréchique à sub bréchique, veinules et cheveux de carbonates, légère altération en calcite, chlorite et hématite, séricite, PY fine et arsénopyrite diss	27.00	28.50	D001927	1.50	0.033	0.033
			28.50	30.00	D001928	1.50	0.016	0.016
			30.00	31.50	D001929	1.50	0.962	0.962
			31.50	33.00	D001930	1.50	0.019	0.019
			33.00	34.50	D001931	1.50	0.023	0.023
			34.50	36.00	D001932	1.50	0.008	0.008
			36.00	37.50	D001933	1.50	0.056	0.056
			37.50	39.00	D001934	1.50	0.042	0.042
			39.00	40.50	D001935	1.50	0.006	0.006
			40.50	42.00	D001937	1.50	0.005	0.005
			42.00	43.50	D001938	1.50	0.006	0.006
			43.50	45.00	D001939	1.50	<0.005	0.001
			45.00	46.50	D001940	1.50	<0.005	0.001
45.20	45.60	SY; SY; BRI	46.50	48.00	D001941	1.50	0.167	0.167
		<b>Syénite; Syénite; Brèche intrusive</b>	48.00	49.50	D001942	1.50	0.024	0.024
		bréchique à sub bréchique avec fragments anguleux, carbonates, CL++	49.50	51.00	D001943	1.50	2.490	2.490
			51.00	52.50	D001944	1.50	3.530	3.760
							3.76	

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	52.50	54.00	D001945	1.50	0.114		0.114
	54.00	55.50	D001947	1.50	0.386		0.386
	55.50	57.00	D001948	1.50	0.334		0.334
	57.00	58.50	D001949	1.50	0.162		0.162
	58.50	60.00	D001950	1.50	0.724		0.724
	60.00	61.50	D001951	1.50	1.395		1.395
	61.50	63.00	D001952	1.50	1.005		1.005
	63.00	64.50	D001953	1.50	6.050	5.96	5.960
	64.50	66.00	D001954	1.50	3.430	3.57	3.570
	66.00	67.50	D001955	1.50	0.480		0.480
	67.50	69.00	D001957	1.50	0.252		0.252
	69.00	70.50	D001958	1.50	0.344		0.344
	70.50	72.20	D001959	1.70	0.125		0.125
	72.20	73.50	D001960	1.30	0.031		0.031
	73.50	75.00	D001961	1.50	0.091		0.091
	75.00	76.50	D001962	1.50	0.177		0.177
	76.50	78.00	D001963	1.50	0.219		0.219
	78.00	79.50	D001964	1.50	0.018		0.018
	79.50	81.00	D001965	1.50	0.066		0.066
	81.00	82.50	D001967	1.50	0.007		0.007
	82.50	84.00	D001968	1.50	0.090		0.090
	84.00	85.50	D001969	1.50	0.041		0.041
	85.50	87.00	D001970	1.50	<0.005		0.001
	87.00	88.50	D001971	1.50	0.009		0.009
	88.50	90.00	D001972	1.50	0.005		0.005
	90.00	91.00	D001973	1.00	0.062		0.062
	91.00	92.00	D001974	1.00	0.052		0.052
	92.00	93.50	D001975	1.50	0.124		0.124
	93.50	95.00	D001977	1.50	0.176		0.176
	95.00	96.50	D001978	1.50	0.032		0.032
	96.50	98.00	D001979	1.50	0.147		0.147
	98.00	99.50	D001980	1.50	0.019		0.019
	99.50	101.00	D001981	1.50	0.020		0.020



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			101.00	102.50	D001982	1.50		0.033	0.033
			102.50	104.00	D001983	1.50		0.017	0.017
			104.00	105.50	D001984	1.50		<0.005	0.001
			105.50	107.00	D001985	1.50		<0.005	0.001
			107.00	108.50	D001987	1.50		0.084	0.084
			108.50	110.00	D001988	1.50		0.037	0.037
			110.00	111.60	D001989	1.60		0.031	0.031
			111.60	113.00	D001990	1.40		0.007	0.007
			113.00	114.50	D001991	1.50		<0.005	0.001
			114.50	115.50	D001992	1.00		<0.005	0.001
			115.50	116.70	D001993	1.20		<0.005	0.001
116.30	116.70	SY; BRC <b>Syénite; Brèche de coulée</b> bréchification à fragments mm, gris pâle à rosé, cheveux en reseaux chloritisé							
116.70	175.10	BA; MAS; AMY <b>Basalte 40°; Roche massive; Amygdalaire</b> légèrement verdâtre, localement cisailé, veinules et cheveux de calcite, amydules mm carbonaté, Chlorite, PY fine irrég diss	116.70	118.00	D001994	1.30		0.020	0.020
			118.00	119.50	D001995	1.50		0.024	0.024
			119.50	121.00	D001997	1.50		0.034	0.034
			121.00	122.50	D001998	1.50		0.008	0.008
			122.50	123.80	D001999	1.30		<0.005	0.001
			123.80	125.00	D002000	1.20		<0.005	0.001
			125.00	126.50	D002001	1.50		0.008	0.008
			126.50	128.00	D002002	1.50		<0.005	0.001
			128.00	129.20	D002003	1.20		<0.005	0.001
			129.20	130.50	D002004	1.30		0.007	0.007
			130.50	132.00	D002005	1.50		<0.005	0.001
			132.00	133.50	D002007	1.50		<0.005	0.001
			133.50	135.00	D002008	1.50		<0.005	0.001
			135.00	136.50	D002009	1.50		<0.005	0.001
			136.50	138.00	D002010	1.50		<0.005	0.001
			138.00	139.50	D002011	1.50		<0.005	0.001
			139.50	141.00	D002012	1.50		<0.005	0.001
			141.00	142.50	D002013	1.50		0.169	0.169
			142.50	144.00	D002014	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			144.00	145.50	D002015	1.50	<0.005		0.001
			145.50	147.00	D002017	1.50	<0.005		0.001
			147.00	148.50	D002018	1.50	<0.005		0.001
			148.50	150.00	D002019	1.50	<0.005		0.001
			150.00	151.50	D002020	1.50	<0.005		0.001
			151.50	153.00	D002021	1.50	0.017		0.017
			153.00	154.50	D002022	1.50	<0.005		0.001
			154.50	156.00	D002023	1.50	0.012		0.012
			156.00	157.50	D002024	1.50	<0.005		0.001
			157.50	159.00	D002025	1.50	<0.005		0.001
			159.00	160.50	D002027	1.50	<0.005		0.001
			160.50	162.00	D002028	1.50	<0.005		0.001
			162.00	163.50	D002029	1.50	<0.005		0.001
			163.50	165.00	D002030	1.50	<0.005		0.001
			165.00	166.50	D002031	1.50	<0.005		0.001
			166.50	168.00	D002032	1.50	<0.005		0.001
			168.00	169.50	D002033	1.50	0.022		0.022
			169.50	171.00	D002034	1.50	<0.005		0.001
			171.00	172.50	D002035	1.50	<0.005		0.001
			172.50	174.00	D002037	1.50	0.006		0.006
			174.00	175.10	D002038	1.10	0.031		0.031
116.70	129.20	BA; BRC <b>Basalte 40°; Brèche de coulée</b> Tuf rhyolitique silicifié, passage felsique gris pâle à teinte rosé, bréchique à sub bréchique, aspect cherteux, localement pseudo litage, fragmenté							
175.10	178.50	GR; FIN; MAS <b>Grès 40°; Grains fins; Roche massive</b> induré légèrement silicifié, biotite pervasive, localement bréchifié, litage 30-40° ac, passge graphiteux, fragments mêlés, veines et veinules de QZ,	175.10	176.10	D002039	1.00	0.446		0.446
			176.10	177.00	D002040	0.90	4.520	4.58	4.580
			177.00	178.50	D002041	1.50	2.060		2.060
178.50	179.50	TU <b>Tuf à cristaux felsique 50°</b> grains fin légèrement silicifié, gris rosâtre en fin d'éch, fragment cm en oillet, CL+, K+, PY en amas fine	178.50	179.50	D002042	1.00	0.143		0.143

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
179.50	183.60	GR; MAS; FIN <b>Grès 50°; Roche massive; Grains fins</b> grès fin à mudstone, localement altéré en silice, passage graphiteux biotite pervasive, veinules et cheveux de QZ et calcite, cheveux en reseaux, PY en amas et fine	179.50	181.00	D002043	1.50	0.788		0.788
			181.00	182.30	D002044	1.30	0.315		0.315
			182.30	183.60	D002045	1.30	0.312		0.312
183.60	189.40	BA; MAS; AMY <b>Basalte 50°; Roche massive; Amygdalaire</b> légèrement chloritisé, amygdules carbonaté, veines, veinules et cheveux de calcite cm, localement silicification, PY en amas et fine diss	183.60	185.00	D002047	1.40	0.009	5.07	0.009
			185.00	186.50	D002048	1.50	<0.005		0.001
			186.50	188.00	D002049	1.50	<0.005		0.001
189.40	195.00	GR; MAS; FIN <b>Grès 30°; Roche massive; Grains fins</b> sediments localement bréchifié, veinules de calcite hématisé avec PY fine, cheveux en reseaux ou sub // , biotite pervasive, PY en amas et fine diss	188.00	189.40	D002050	1.40	5.350	4.13	5.070
			189.40	191.00	D002051	1.60	2.090		2.090
			191.00	192.50	D002052	1.50	4.400		4.130
			192.50	194.00	D002053	1.50	2.710		2.710
195.00	260.10	TU; FIN <b>Tuf à cendre/lapillis 30°; Grains fins</b> grains fin à très fin, localement litage 30-40° ac, laminations, laminations de graphite, localement bréchifié, lentilles de carbonâtes cm, cheveux 30-40° ac, CL++, PY en amas et fine diss	194.00	195.00	D002054	1.00	1.230		1.230
			195.00	196.50	D002055	1.50	0.275		0.275
			196.50	198.00	D002057	1.50	0.021		0.021
			198.00	199.50	D002058	1.50	0.013		0.013
			199.50	201.00	D002059	1.50	0.342		0.342
200.75	200.80	FAI <b>Faille 30°</b> boue de failles verdâtre	201.00	202.50	D002060	1.50	0.007		0.007
			202.50	204.00	D002061	1.50	<0.005		0.001
			204.00	205.00	D002062	1.00	<0.005		0.001
			205.00	206.20	D002063	1.20	0.006		0.006
			206.20	207.50	D002064	1.30	0.019		0.019
			207.50	209.00	D002065	1.50	0.011		0.011
			209.00	210.50	D002067	1.50	<0.005		0.001
			210.50	212.00	D002068	1.50	0.007		0.007
213.00	214.20	TU; LAM; FIN <b>Tuf à cristaux mafique; Laminations parallèles;</b> <b>Grains fins</b> veines et veines de calcite 70-80° ac, lames de graphite, chloritisation, altération en calcite, chalcopryrite	212.00	213.00	D002069	1.00	<0.005		0.001
			213.00	214.20	D002070	1.20	<0.005		0.001
			214.20	215.30	D002071	1.10	0.009		0.009
215.30	220.00	TU; FIN; LAM <b>Tuf à cristaux mafique; Grains fins; Laminations</b> <b>parallèles</b> lentilles de carbonâtes, laminations de graphite à 30° ac, CL++,	215.30	216.50	D002072	1.20	<0.005		0.001
			216.50	218.00	D002073	1.50	<0.005		0.001
			218.00	219.00	D002074	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
PY en amas diss	219.00	220.00	D002075	1.00	<0.005		0.001
	220.00	221.50	D002077	1.50	<0.005		0.001
	221.50	223.00	D002078	1.50	<0.005		0.001
	223.00	224.50	D002079	1.50	<0.005		0.001
	224.50	226.00	D002080	1.50	<0.005		0.001
	226.00	227.50	D002081	1.50	0.010		0.010
	227.50	229.00	D002082	1.50	<0.005		0.001
	229.00	230.50	D002083	1.50	<0.005		0.001
	230.50	232.00	D002084	1.50	<0.005		0.001
	232.00	233.50	D002085	1.50	<0.005		0.001
	233.50	235.00	D002087	1.50	<0.005		0.001
	235.00	236.50	D002088	1.50	<0.005		0.001
	236.50	238.00	D002089	1.50	<0.005		0.001
	238.00	239.50	D002090	1.50	<0.005		0.001
	239.50	241.00	D002091	1.50	<0.005		0.001
	241.00	242.50	D002092	1.50	<0.005		0.001
	242.50	244.00	D002093	1.50	0.005		0.005
	244.00	245.50	D002094	1.50	<0.005		0.001
	245.50	247.00	D002095	1.50	<0.005		0.001
	247.00	248.00	D002097	1.00	<0.005		0.001
	248.00	249.50	D002098	1.50	0.009		0.009
	249.50	251.00	D002099	1.50	0.028		0.028
	251.00	252.00	D002100	1.00	<0.005		0.001
	252.00	253.60	D002101	1.60	<0.005		0.001
	253.60	255.00	D002102	1.40	<0.005		0.001
	255.00	256.50	D002103	1.50	<0.005		0.001
	256.50	258.00	D002104	1.50	<0.005		0.001
	258.00	259.00	D002105	1.00	<0.005		0.001
259.00	260.10	D002107	1.10	<0.005		0.001	
260.10      268.80      BA; MAS <b>Basalte 40°; Roche massive</b> massive gris pâle à verdâtre, localement rosé à phénocristaux de FP( plagioclase), veines et veinules de calcite, CL+++ , K+, fortement altéré en calcite,	260.10	261.50	D002108	1.40	0.007		0.007
	261.50	263.00	D002109	1.50	0.008		0.008
	263.00	264.50	D002110	1.50	0.013		0.013
	264.50	266.00	D002111	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
260.10	264.50	BA; POR <b>Basalte 40°; Porphyrique</b> microlitique, matrice gris foncé, phénocristaux automorphe de FP 0.2-1 cm blanc, localement légèrement bréchifié avec altération potassique	266.00	267.50	D002112	1.50	<0.005		0.001
			267.50	268.80	D002113	1.30	<0.005		0.001
268.80	292.70	TU; LAM; BRC <b>Tuf à cendre/lapillis 40°; Laminations parallèles; Brèche de coulée</b> laminations gris foncé, bréchifications à fragments anguleux verdâtre, lentilles decarbonates, passage massif induré altéré en chlorite, fortement altéré en calcite, PY en amas et fine diss	268.80	270.00	D002114	1.20	<0.005		0.001
			270.00	271.50	D002115	1.50	<0.005		0.001
			271.50	273.00	D002117	1.50	<0.005		0.001
			273.00	274.50	D002118	1.50	<0.005		0.001
			274.50	276.00	D002119	1.50	<0.005		0.001
			276.00	277.50	D002120	1.50	<0.005		0.001
			277.50	279.00	D002121	1.50	<0.005		0.001
			279.00	280.50	D002122	1.50	<0.005		0.001
			280.50	282.00	D002123	1.50	<0.005		0.001
			282.00	283.50	D002124	1.50	<0.005		0.001
			283.50	285.00	D002125	1.50	<0.005		0.001
			285.00	286.50	D002127	1.50	<0.005		0.001
			286.50	288.00	D002128	1.50	<0.005		0.001
			288.00	289.50	D002129	1.50	<0.005		0.001
268.80	276.00	TU; BRC <b>Tuf à cendre/lapillis 40°; Brèche de coulée</b> brèches à fragments cm anguleux, lamines fine grisâtre moins induré, veines de calcite, PY fine diss	289.50	291.00	D002130	1.50	<0.005		0.001
			291.00	292.50	D002131	1.50	0.005		0.005
			292.50	293.60	D002132	1.10	0.240		0.240
			293.60	295.00	D002133	1.40	<0.005		0.001
			295.00	296.30	D002134	1.30	0.018		0.018
292.70	300.70	GR; FIN <b>Grès 50°; Grains fins</b> grès fin graphiteux, localement fines laminations brunâtre, veines de carbonates metrique, fragments mêlés, PY et chalcopryite en amas et fine	296.30	297.50	D002135	1.20	0.022		0.022
			297.50	299.00	D002137	1.50	0.053		0.053
			299.00	300.70	D002138	1.70	0.006		0.006
			300.70	302.00	D002139	1.30	<0.005		0.001
300.70	333.80	BA; MAS; FIN; AMY <b>Basalte 50°; Roche massive; Grains fins; Amygdalaire</b>	302.00	303.50	D002140	1.50	<0.005		0.001
			303.50						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		verdâtre, légèrement cisailé amygdules de carbonâtes, veine veinules et cheveux de carbonâte, altération en calcite et chloritisation	303.50	305.00	D002141	1.50	<0.005		0.001
			305.00	306.50	D002142	1.50	<0.005		0.001
			306.50	308.00	D002143	1.50	<0.005		0.001
			308.00	309.50	D002144	1.50	<0.005		0.001
			309.50	311.00	D002145	1.50	<0.005		0.001
			311.00	312.50	D002147	1.50	<0.005		0.001
			312.50	314.00	D002148	1.50	0.055		0.055
			314.00	315.50	D002149	1.50	<0.005		0.001
			315.50	317.00	D002150	1.50	0.055		0.055
			317.00	318.50	D002151	1.50	<0.005		0.001
			318.50	320.00	D002152	1.50	<0.005		0.001
			320.00	321.50	D002153	1.50	<0.005		0.001
			321.50	323.00	D002154	1.50	<0.005		0.001
			323.00	324.50	D002155	1.50	<0.005		0.001
			324.50	326.00	D002157	1.50	<0.005		0.001
			326.00	327.50	D002158	1.50	<0.005		0.001
			327.50	329.00	D002159	1.50	<0.005		0.001
			329.00	330.50	D002160	1.50	<0.005		0.001
			330.50	331.80	D002161	1.30	<0.005		0.001
			331.80	332.80	D002162	1.00	<0.005		0.001
			332.80	333.80	D002163	1.00	<0.005		0.001
333.80	336.90	GR; MAS; FIN <b>Grès 50°; Roche massive; Grains fins</b> légèrement cisailé, laminations, lentille de calcite, , graphite, CL++, PY en amas fin ,	333.80	335.00	D002164	1.20	0.005		0.005
			335.00	336.00	D002165	1.00	<0.005		0.001
334.17	334.20	FAI <b>Faille 50°</b> boue noir de graphite	336.00	336.90	D002167	0.90	<0.005		0.001
336.90	338.10	BA; MAS; AMY <b>Basalte 30°; Roche massive; Amygdalaire</b> localement laminations 30° ac, cheveux carbonâté, amygdules carbonâté, PY en amas fin diss	336.90	338.10	D002168	1.20	<0.005		0.001
338.10	343.30	GR; LAM <b>Grès 30°; Laminations parallèles</b> laminations 20-40° ac, localement plissé, cheveux et veinules localement //, lentilles de carbonâtes, BO+, graphite, chlorite, PY en	338.10	339.50	D002169	1.40	<0.005		0.001
			339.50	341.00	D002170	1.50	<0.005		0.001
			341.00	342.00	D002171	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		amas fin diss	342.00	343.30	D002172	1.30	<0.005		0.001
343.30	344.60	BA; MAS; AMY <b>Basalte 40°; Roche massive; Amygdalaire</b> lentilles de carbonâtes, légèrement cisaillé, amygdules carbonaté, veinules et cheveux de carbonâtes	343.30	344.60	D002173	1.30	<0.005		0.001
344.60	346.00	GR; LAM <b>Grès 30°; Laminations parallèles</b> laminations 10-30° ac, graphite, BO++, cheveux pyritisé, PY en amas fin diss	344.60	346.00	D002174	1.40	<0.005		0.001
346.00	347.00	BA; MAS; AMY <b>Basalte 20°; Roche massive; Amygdalaire</b> amygdules carbonaté, carbonâtes CL++, calcite, CL+++	346.00	347.00	D002175	1.00	<0.005		0.001
347.00	Fin du sondage Nombre d'échantillons : 234 Nombre d'échantillons QAQC : 25 Longueur totale échantillonnée : 333.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
25.50	27.00	D001926	D001925	1.50	<0.005	0.001
39.00	40.50	D001936	A3	1.50	0.586	0.586
52.50	54.00	D001946	D001945	1.50	0.106	0.106
66.00	67.50	D001956	M1	1.50	<0.005	0.001
79.50	81.00	D001966	D001965	1.50	0.045	0.045
92.00	93.50	D001976	B4	1.50	2.580	2.580
105.50	107.00	D001986	D001985	1.50	<0.005	0.001
118.00	119.50	D001996	M1	1.50	<0.005	0.001
130.50	132.00	D002006	D002005	1.50	<0.005	0.001
144.00	145.50	D002016	C4	1.50	1.300	1.300
157.50	159.00	D002026	D002025	1.50	<0.005	0.001
171.00	172.50	D002036	M1	1.50	<0.005	0.001
182.30	183.60	D002046	D002045	1.30	0.348	0.348
195.00	196.50	D002056	D2	1.50	0.890	0.890
207.50	209.00	D002066	D002065	1.50	0.012	0.012
219.00	220.00	D002076	M1	1.00	<0.005	0.001
232.00	233.50	D002086	D002085	1.50	<0.005	0.001
245.50	247.00	D002096	F2	1.50	8.210	8.440
258.00	259.00	D002106	D002105	1.00	<0.005	0.001
270.00	271.50	D002116	M1	1.50	<0.005	0.001
283.50	285.00	D002126	D002125	1.50	<0.005	0.001
296.30	297.50	D002136	G2	1.20	3.810	4.000
309.50	311.00	D002146	D002145	1.50	<0.005	0.001
323.00	324.50	D002156	M1	1.50	<0.005	0.001
335.00	336.00	D002166	D002165	1.00	<0.005	0.001



## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-155</b>	Titre minier :	Section :	630000
	Canton :	Niveau :	
	Rang :	Place de travail :	
Foré par : Bradley	Lot :		
Décrit par : David RUHARA	Du : 2010-04-06	Date de description :	2010-04-29
	Au : 2010-04-10		

Collet

Azimut : 180.00°  
 Plongée : -60.00°  
 Longueur : 266.00 m

UTM

Est	629 999.8
Nord	5 374 250.0
Élévation	282.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	59.00°	-58.40°	Oui
Reflex	8.00	177.20°	-58.60°	Oui
Reflex	11.00	181.60°	-59.10°	Non
Reflex	14.00	183.20°	-59.10°	Non
Reflex	17.00	182.80°	-59.00°	Non
Reflex	20.00	181.80°	-58.80°	Non
Reflex	23.00	182.40°	-58.60°	Non
Reflex	26.00	181.20°	-58.60°	Non
Reflex	29.00	181.80°	-58.50°	Non
Reflex	32.00	182.90°	-58.50°	Non
Reflex	35.00	180.90°	-58.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	181.30°	-58.40°	Non
Reflex	41.00	181.80°	-58.20°	Non
Reflex	44.00	182.00°	-58.20°	Non
Reflex	47.00	181.80°	-57.70°	Non
Reflex	50.00	181.50°	-57.80°	Non
Reflex	53.00	181.70°	-57.80°	Non
Reflex	56.00	181.60°	-57.80°	Non
Reflex	59.00	181.70°	-57.70°	Non
Reflex	62.00	181.90°	-57.70°	Non
Reflex	65.00	182.10°	-57.90°	Non
Reflex	68.00	182.30°	-57.90°	Non
Reflex	71.00	182.30°	-57.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	182.10°	-57.60°	Non	Reflex	173.00	182.20°	-54.70°	Non
Reflex	77.00	182.60°	-57.70°	Non	Reflex	176.00	182.30°	-54.60°	Non
Reflex	80.00	182.60°	-57.60°	Non	Reflex	179.00	182.30°	-54.30°	Non
Reflex	83.00	182.40°	-57.60°	Non	Reflex	182.00	182.90°	-54.40°	Non
Reflex	86.00	182.60°	-57.60°	Non	Reflex	185.00	183.00°	-54.60°	Non
Reflex	89.00	182.70°	-57.60°	Non	Reflex	188.00	183.10°	-54.50°	Non
Reflex	92.00	182.40°	-57.50°	Non	Reflex	191.00	182.90°	-54.30°	Non
Reflex	95.00	182.20°	-57.60°	Non	Reflex	194.00	183.30°	-54.10°	Non
Reflex	98.00	182.80°	-57.70°	Non	Reflex	197.00	183.10°	-54.10°	Non
Reflex	101.00	182.60°	-57.40°	Non	Reflex	200.00	183.40°	-54.00°	Non
Reflex	104.00	182.80°	-57.60°	Non	Reflex	203.00	183.60°	-54.10°	Non
Reflex	107.00	182.50°	-57.30°	Non	Reflex	206.00	182.80°	-54.00°	Non
Reflex	110.00	182.70°	-57.30°	Non	Reflex	209.00	183.10°	-53.80°	Non
Reflex	113.00	183.00°	-57.30°	Non	Reflex	212.00	183.20°	-53.90°	Non
Reflex	116.00	183.10°	-57.20°	Non	Reflex	215.00	183.70°	-53.80°	Non
Reflex	119.00	183.30°	-56.90°	Non	Reflex	218.00	183.10°	-53.70°	Non
Reflex	122.00	183.30°	-56.80°	Non	Reflex	221.00	183.40°	-53.60°	Non
Reflex	125.00	183.10°	-56.60°	Non	Reflex	224.00	183.80°	-53.80°	Non
Reflex	128.00	183.00°	-56.40°	Non	Reflex	227.00	183.20°	-53.60°	Non
Reflex	131.00	183.30°	-56.30°	Non	Reflex	230.00	183.40°	-53.60°	Non
Reflex	134.00	183.30°	-56.10°	Non	Reflex	233.00	183.70°	-53.60°	Non
Reflex	137.00	183.60°	-56.10°	Non	Reflex	236.00	183.10°	-53.50°	Non
Reflex	140.00	183.70°	-56.00°	Non	Reflex	239.00	183.50°	-53.40°	Non
Reflex	143.00	183.90°	-56.00°	Non	Reflex	242.00	183.90°	-53.40°	Non
Reflex	146.00	183.20°	-55.70°	Non	Reflex	245.00	183.10°	-53.30°	Non
Reflex	149.00	184.10°	-55.70°	Non	Reflex	248.00	183.60°	-53.10°	Non
Reflex	152.00	183.30°	-55.40°	Non	Reflex	251.00	183.60°	-53.20°	Non
Reflex	155.00	183.50°	-55.50°	Non	Reflex	254.00	183.40°	-53.00°	Non
Reflex	158.00	183.00°	-55.50°	Non	Reflex	257.00	183.50°	-53.00°	Non
Reflex	161.00	183.30°	-55.20°	Non	Reflex	260.00	183.40°	-52.90°	Non
Reflex	164.00	182.50°	-54.90°	Non	Reflex	263.00	183.80°	-52.70°	Non
Reflex	167.00	182.80°	-54.90°	Non	Reflex	266.00	183.70°	-52.70°	Non
Reflex	170.00	182.20°	-54.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	11.50	MT						
		<b>Mort-terrain</b>						
11.50	41.00	SY; FIN; POR	11.50	13.00	D007854	1.50	0.030	0.030
		<b>Syénite; Grains fins; Porphyrique</b>	13.00	14.50	D007855	1.50	0.024	0.024
		Syénite à grains fins et porphyrique sporadiquement avec de phénocristaux Xmm.	14.50	16.00	D007856	1.50	0.015	0.015
			16.00	17.50	D007858	1.50	<0.005	0.001
			17.50	19.00	D007859	1.50	<0.005	0.001
			19.00	20.50	D007860	1.50	<0.005	0.001
			20.50	22.00	D007861	1.50	<0.005	0.001
			22.00	23.50	D007862	1.50	0.011	0.011
			23.50	25.00	D007863	1.50	0.296	0.296
			25.00	26.50	D007864	1.50	0.481	0.481
			26.50	28.00	D007865	1.50	<0.005	0.001
			28.00	29.50	D007866	1.50	<0.005	0.001
			29.50	31.00	D007868	1.50	<0.005	0.001
			31.00	32.50	D007869	1.50	<0.005	0.001
			32.50	34.00	D007870	1.50	0.005	0.005
			34.00	35.50	D007871	1.50	0.005	0.005
			35.50	37.00	D007872	1.50	0.007	0.007
			37.00	38.00	D007873	1.00	0.025	0.025
			38.00	39.00	D007874	1.00	0.016	0.016
			39.00	40.00	D007875	1.00	0.011	0.011
			40.00	41.00	D007876	1.00	<0.005	0.001
41.00	65.50	GW; FIN; RUB	41.00	42.00	D007878	1.00	0.017	0.017
		<b>Grauwacke; Grains fins; Rubané</b>	42.00	43.50	D007879	1.50	0.011	0.011
		Grauwacke, à grains fins, lité et rubané.	43.50	45.00	D007880	1.50	0.012	0.012
			45.00	46.50	D007881	1.50	0.503	0.503
			46.50	48.00	D007883	1.50	0.113	0.113
			48.00	49.50	D007884	1.50	0.266	0.266
			49.50	51.00	D007885	1.50	0.062	0.062
			51.00	52.50	D007886	1.50	0.231	0.231
			52.50	54.00	D007888	1.50	0.176	0.176
			54.00	55.50	D007889	1.50	0.047	0.047

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
65.50	104.60	UM; APH; RUB <b>Ultramaïfite serpentinisée; Aphanitique; Rubané</b> Ultramaïfique serpentinisée, talqueuse, aphanitique ,rubanée et cisailée.	55.50	57.00	D007890	1.50	0.044		0.044
			57.00	58.50	D007891	1.50	0.045		0.045
			58.50	60.00	D007892	1.50	0.011		0.011
			60.00	61.50	D007893	1.50	0.009		0.009
			61.50	63.00	D007894	1.50	0.050		0.050
			63.00	64.00	D007895	1.00	0.151		0.151
			64.00	65.50	D007896	1.50	0.070		0.070
			65.50	67.00	D007898	1.50	0.007		0.007
			67.00	68.50	D007899	1.50	<0.005		0.001
			68.50	70.00	D007900	1.50	<0.005		0.001
			70.00	71.50	D007901	1.50	0.006		0.006
			71.50	73.00	D007902	1.50	<0.005		0.001
			73.00	74.50	D007903	1.50	0.007		0.007
			74.50	76.00	D007904	1.50	0.013		0.013
			76.00	77.50	D007905	1.50	<0.005		0.001
			77.50	79.00	D007906	1.50	<0.005		0.001
			79.00	80.50	D007908	1.50	0.006		0.006
			80.50	82.00	D007909	1.50	0.006		0.006
			82.00	83.50	D007910	1.50	<0.005		0.001
			83.50	85.00	D007911	1.50	<0.005		0.001
			85.00	86.50	D007912	1.50	<0.005		0.001
			86.50	88.00	D007913	1.50	<0.005		0.001
			88.00	89.50	D007914	1.50	<0.005		0.001
			89.50	91.00	D007915	1.50	<0.005		0.001
			91.00	92.50	D007916	1.50	0.006		0.006
			92.50	94.00	D007918	1.50	<0.005		0.001
94.00	95.50	D007919	1.50	<0.005		0.001			
95.50	97.00	D007920	1.50	<0.005		0.001			
97.00	98.50	D007921	1.50	<0.005		0.001			
98.50	100.00	D007923	1.50	<0.005		0.001			
100.00	101.50	D007924	1.50	<0.005		0.001			
101.50	103.00	D007925	1.50	<0.005		0.001			
103.00	104.60	D007926	1.60	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
104.60	266.00	TU; MAS; RUB <b>Tuf à cendre/lapillis 55°; Roche massive; Rubané</b> Tuf à cendre/lapillis, massive, rubanée et cisailé.	104.60	106.00	D007928	1.40	0.008		0.008
			106.00	107.50	D007929	1.50	0.027		0.027
			107.50	109.00	D007930	1.50	0.009		0.009
			109.00	110.50	D007931	1.50	0.008		0.008
			110.50	112.00	D007932	1.50	0.007		0.007
			112.00	113.50	D007933	1.50	0.008		0.008
			113.50	115.00	D007934	1.50	0.008		0.008
			115.00	116.50	D007935	1.50	0.015		0.015
			116.50	118.00	D007936	1.50	0.166		0.166
			118.00	119.50	D007938	1.50	0.294		0.294
			119.50	121.00	D007939	1.50	0.273		0.273
			121.00	122.50	D007940	1.50	0.217		0.217
			122.50	124.00	D007941	1.50	0.017		0.017
			124.00	125.50	D007942	1.50	0.021		0.021
			125.50	127.00	D007943	1.50	0.072		0.072
			127.00	128.50	D007944	1.50	0.007		0.007
			128.50	130.00	D007945	1.50	0.060		0.060
			130.00	131.50	D007946	1.50	0.047		0.047
			131.50	133.00	D007948	1.50	0.014		0.014
			133.00	134.50	D007949	1.50	0.014		0.014
			134.50	136.00	D007950	1.50	0.070		0.070
			136.00	137.50	D007951	1.50	0.290		0.290
			137.50	139.00	D007952	1.50	0.220		0.220
			139.00	140.50	D007953	1.50	0.045		0.045
			140.50	142.00	D007954	1.50	0.010		0.010
			142.00	143.50	D007955	1.50	0.074		0.074
143.50	145.00	D007956	1.50	0.007		0.007			
145.00	146.50	D007958	1.50	0.029		0.029			
146.50	148.00	D007959	1.50	0.074		0.074			
148.00	149.50	D007960	1.50	0.157		0.157			
149.50	151.00	D007961	1.50	0.049		0.049			
151.00	152.50	D007963	1.50	0.122		0.122			
152.50	154.00	D007964	1.50	0.022		0.022			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	154.00	155.50	D007965	1.50	0.018		0.018
	155.50	157.00	D007966	1.50	0.006		0.006
	157.00	158.50	D007968	1.50	0.008		0.008
	158.50	160.00	D007969	1.50	0.015		0.015
	160.00	161.50	D007970	1.50	0.009		0.009
	161.50	163.00	D007971	1.50	0.008		0.008
	163.00	164.50	D007972	1.50	0.013		0.013
	164.50	166.00	D007973	1.50	0.105		0.105
	166.00	167.50	D007974	1.50	0.047		0.047
	167.50	169.00	D007975	1.50	0.171		0.171
	169.00	170.50	D007976	1.50	0.154		0.154
	170.50	172.00	D007978	1.50	0.104		0.104
	172.00	173.50	D007979	1.50	0.106		0.106
	173.50	175.00	D007980	1.50	0.039		0.039
	175.00	176.50	D007981	1.50	0.007		0.007
	176.50	178.00	D007982	1.50	0.015		0.015
	178.00	179.50	D007983	1.50	0.106		0.106
	179.50	181.00	D007984	1.50	0.008		0.008
	181.00	182.50	D007985	1.50	0.008		0.008
	182.50	184.00	D007986	1.50	0.007		0.007
	184.00	185.50	D007988	1.50	0.007		0.007
	185.50	187.00	D007989	1.50	0.008		0.008
	187.00	188.50	D007990	1.50	0.005		0.005
	188.50	190.00	D007991	1.50	0.005		0.005
	190.00	191.50	D007992	1.50	0.009		0.009
	191.50	193.00	D007993	1.50	0.006		0.006
	193.00	194.50	D007994	1.50	0.014		0.014
	194.50	196.00	D007995	1.50	0.008		0.008
	196.00	197.50	D007996	1.50	0.071		0.071
	197.50	199.00	D007998	1.50	0.024		0.024
	199.00	200.50	D007999	1.50	0.047		0.047
	200.50	202.00	D008000	1.50	0.099		0.099
	202.00	203.50	D008001	1.50	0.123		0.123

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	203.50	205.00	D008003	1.50	0.259		0.259
	205.00	206.50	D008004	1.50	0.015		0.015
	206.50	208.00	D008005	1.50	0.017		0.017
	208.00	209.50	D008006	1.50	0.010		0.010
	209.50	211.00	D008008	1.50	0.022		0.022
	211.00	212.50	D008009	1.50	<0.005		0.001
	212.50	214.00	D008010	1.50	0.015		0.015
	214.00	215.50	D008011	1.50	0.009		0.009
	215.50	217.00	D008012	1.50	0.006		0.006
	217.00	218.50	D008013	1.50	0.006		0.006
	218.50	220.00	D008014	1.50	0.010		0.010
	220.00	221.50	D008015	1.50	0.048		0.048
	221.50	223.00	D008016	1.50	0.028		0.028
	223.00	224.50	D008018	1.50	0.017		0.017
	224.50	226.00	D008019	1.50	0.014		0.014
	226.00	227.50	D008020	1.50	<0.005		0.001
	227.50	229.00	D008021	1.50	<0.005		0.001
	229.00	230.50	D008022	1.50	0.025		0.025
	230.50	232.00	D008023	1.50	0.005		0.005
	232.00	233.50	D008024	1.50	0.017		0.017
	233.50	235.00	D008025	1.50	0.006		0.006
	235.00	236.50	D008026	1.50	<0.005		0.001
	236.50	238.00	D008028	1.50	<0.005		0.001
	238.00	239.50	D008029	1.50	0.005		0.005
	239.50	241.00	D008030	1.50	0.005		0.005
	241.00	242.50	D008031	1.50	<0.005		0.001
	242.50	244.00	D008032	1.50	<0.005		0.001
	244.00	245.60	D008033	1.60	<0.005		0.001
	245.60	247.00	D008034	1.40	<0.005		0.001
	247.00	248.50	D008035	1.50	<0.005		0.001
	248.50	250.00	D008036	1.50	<0.005		0.001
	250.00	251.00	D008038	1.00	<0.005		0.001
	251.00	252.50	D008039	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	252.50	254.00	D008040	1.50	0.006		0.006
	254.00	255.50	D008041	1.50	0.005		0.005
	255.50	257.00	D008043	1.50	0.005		0.005
	257.00	258.50	D008044	1.50	0.006		0.006
	258.50	260.00	D008045	1.50	0.012		0.012
	260.00	261.50	D008046	1.50	<0.005		0.001
	261.50	263.00	D008048	1.50	0.035		0.035
	263.00	264.50	D008049	1.50	0.030		0.030
	264.50	266.00	D008050	1.50	<0.005		0.001
266.00	Fin du sondage Nombre d'échantillons : 172 Nombre d'échantillons QAQC : 25 Longueur totale échantillonnée : 254.50						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	16.00	D007857	D007856	1.50	0.017	0.017
28.00	29.50	D007867	C4	1.50	1.245	1.245
40.00	41.00	D007877	D007876	1.00	<0.005	0.001
45.00	45.00	D007882	M1	0.00	<0.005	0.001
51.00	51.00	D007887	D2	0.00	0.866	0.866
64.00	65.50	D007897	D007896	1.50	0.074	0.074
77.50	79.00	D007907	F2	1.50	8.670	8.670
91.00	92.50	D007917	D007916	1.50	<0.005	0.001
97.00	98.50	D007922	M1	1.50	<0.005	0.001
103.00	104.50	D007927	G2	1.50	4.050	4.050
116.50	118.00	D007937	D007936	1.50	0.266	0.266
130.00	131.50	D007947	H	1.50	1.010	1.010
143.50	145.00	D007957	D007956	1.50	0.044	0.044
149.50	151.50	D007962	M1	2.00	<0.005	0.001
155.50	157.00	D007967	A3	1.50	0.590	0.590
169.00	170.50	D007977	D007976	1.50	0.127	0.127
182.50	184.00	D007987	B4	1.50	2.580	2.580
196.00	197.50	D007997	D007996	1.50	0.082	0.082
202.00	203.50	D008002	M1	1.50	<0.005	0.001
208.00	209.50	D008007	C4	1.50	0.945	0.945
221.50	223.00	D008017	D008016	1.50	0.042	0.042
235.00	236.50	D008027	D2	1.50	0.864	0.864
248.50	250.00	D008037	D008036	1.50	<0.005	0.001
254.00	255.50	D008042	M1	1.50	<0.005	0.001
260.00	261.00	D008047	F2	1.00	8.240	8.240

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-156**

Titre minier :

Section :                      630 800

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Ciara Cooke/Guy gbaguidi

Lot :

Du :                              2010-04-07

Date de description :

Au :                              2010-04-12

Collet

UTM

Azimut :                      0.00°

Est                              630 799.1

Plongée :                      -60.00°

Nord                            5 374 449.9

Longueur :                      413.00 m

Élévation                      314.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	3.00°	-60.00°	Non
Reflex	5.00	3.90°	-60.00°	Non
Reflex	8.00	3.20°	-60.10°	Non
Reflex	11.00	3.10°	-60.10°	Non
Reflex	14.00	0.30°	-60.10°	Non
Reflex	17.00	0.80°	-60.20°	Non
Reflex	20.00	1.40°	-60.20°	Non
Reflex	23.00	2.00°	-60.20°	Non
Reflex	26.00	0.70°	-60.20°	Oui
Reflex	29.00	2.90°	-60.20°	Non
Reflex	32.00	2.40°	-60.20°	Non
Reflex	35.00	1.10°	-60.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	3.60°	-60.30°	Non
Reflex	41.00	2.30°	-60.30°	Non
Reflex	44.00	3.50°	-60.30°	Non
Reflex	47.00	2.30°	-60.40°	Non
Reflex	50.00	0.50°	-60.40°	Non
Reflex	53.00	2.40°	-60.40°	Non
Reflex	56.00	2.20°	-60.40°	Non
Reflex	59.00	2.20°	-60.40°	Non
Reflex	62.00	2.30°	-60.40°	Non
Reflex	65.00	0.90°	-60.40°	Non
Reflex	68.00	0.50°	-60.30°	Non
Reflex	71.00	1.40°	-60.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.90°	-60.20°	Non	Reflex	173.00	3.20°	-58.50°	Non
Reflex	77.00	1.30°	-60.30°	Non	Reflex	176.00	2.90°	-58.40°	Non
Reflex	80.00	1.00°	-60.30°	Non	Reflex	179.00	2.40°	-58.40°	Non
Reflex	83.00	2.60°	-60.20°	Non	Reflex	182.00	1.70°	-58.30°	Non
Reflex	86.00	1.60°	-60.30°	Non	Reflex	185.00	2.60°	-58.30°	Non
Reflex	89.00	2.10°	-60.30°	Non	Reflex	188.00	3.50°	-58.10°	Non
Reflex	92.00	2.20°	-60.20°	Non	Reflex	191.00	3.80°	-58.10°	Non
Reflex	95.00	1.90°	-60.20°	Non	Reflex	194.00	5.00°	-58.00°	Non
Reflex	98.00	1.60°	-60.20°	Non	Reflex	197.00	5.20°	-58.00°	Non
Reflex	101.00	1.50°	-60.10°	Non	Reflex	200.00	5.40°	-58.00°	Non
Reflex	104.00	1.60°	-59.90°	Non	Reflex	203.00	6.40°	-57.90°	Non
Reflex	107.00	1.10°	-59.90°	Non	Reflex	206.00	6.20°	-57.90°	Non
Reflex	110.00	1.20°	-59.90°	Non	Reflex	209.00	7.30°	-57.80°	Non
Reflex	113.00	1.20°	-59.90°	Non	Reflex	212.00	7.30°	-57.80°	Non
Reflex	116.00	1.40°	-59.90°	Non	Reflex	215.00	8.20°	-57.80°	Non
Reflex	119.00	1.70°	-59.90°	Non	Reflex	218.00	7.00°	-57.80°	Non
Reflex	122.00	1.60°	-59.90°	Non	Reflex	221.00	6.40°	-57.80°	Non
Reflex	125.00	1.50°	-59.80°	Non	Reflex	224.00	7.40°	-57.70°	Non
Reflex	128.00	1.70°	-59.80°	Non	Reflex	227.00	8.00°	-57.70°	Non
Reflex	131.00	3.20°	-59.70°	Non	Reflex	230.00	7.80°	-57.60°	Non
Reflex	134.00	3.30°	-59.50°	Non	Reflex	233.00	10.40°	-57.60°	Oui
Reflex	137.00	3.30°	-59.50°	Non	Reflex	236.00	9.60°	-57.50°	Non
Reflex	140.00	3.10°	-59.50°	Non	Reflex	239.00	9.70°	-57.40°	Non
Reflex	143.00	2.70°	-59.50°	Non	Reflex	242.00	6.40°	-57.40°	Non
Reflex	146.00	2.20°	-59.30°	Non	Reflex	245.00	7.70°	-57.50°	Non
Reflex	149.00	1.50°	-59.20°	Non	Reflex	248.00	8.80°	-57.50°	Non
Reflex	152.00	3.90°	-59.20°	Non	Reflex	251.00	9.30°	-57.50°	Non
Reflex	155.00	5.30°	-59.10°	Oui	Reflex	254.00	9.00°	-57.50°	Non
Reflex	158.00	4.60°	-59.00°	Oui	Reflex	257.00	10.80°	-57.50°	Non
Reflex	161.00	3.10°	-58.90°	Non	Reflex	260.00	8.10°	-57.50°	Non
Reflex	164.00	4.60°	-58.80°	Non	Reflex	263.00	8.80°	-57.50°	Non
Reflex	167.00	5.40°	-58.70°	Non	Reflex	266.00	11.80°	-57.60°	Non
Reflex	170.00	6.00°	-58.60°	Non	Reflex	269.00	12.00°	-57.60°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	10.90°	-57.60°	Non	Reflex	371.00	11.40°	-55.60°	Non
Reflex	275.00	8.00°	-57.60°	Oui	Reflex	374.00	11.70°	-55.60°	Non
Reflex	278.00	9.80°	-57.60°	Non	Reflex	377.00	11.70°	-55.60°	Non
Reflex	281.00	13.60°	-57.60°	Oui	Reflex	380.00	11.60°	-55.60°	Non
Reflex	284.00	11.30°	-57.60°	Non	Reflex	383.00	11.70°	-55.50°	Non
Reflex	287.00	10.10°	-57.60°	Non	Reflex	386.00	11.70°	-55.50°	Non
Reflex	290.00	10.50°	-57.50°	Non	Reflex	389.00	11.70°	-55.50°	Non
Reflex	293.00	10.40°	-57.50°	Non	Reflex	392.00	11.80°	-55.50°	Non
Reflex	296.00	11.00°	-57.60°	Non	Reflex	395.00	11.70°	-55.40°	Non
Reflex	299.00	11.30°	-57.60°	Non	Reflex	398.00	12.10°	-55.40°	Non
Reflex	302.00	11.40°	-57.50°	Non	Reflex	401.00	12.00°	-55.30°	Non
Reflex	305.00	11.50°	-57.50°	Non	Reflex	404.00	12.00°	-55.30°	Non
Reflex	308.00	11.70°	-57.50°	Non	Reflex	407.00	12.10°	-55.20°	Non
Reflex	311.00	11.70°	-57.40°	Non					
Reflex	314.00	11.70°	-57.30°	Non					
Reflex	317.00	12.20°	-56.60°	Non					
Reflex	320.00	11.90°	-57.60°	Non					
Reflex	323.00	12.90°	-57.40°	Non					
Reflex	326.00	11.50°	-57.10°	Non					
Reflex	329.00	11.60°	-56.90°	Non					
Reflex	332.00	11.50°	-56.70°	Non					
Reflex	335.00	11.40°	-56.60°	Non					
Reflex	338.00	11.40°	-56.40°	Non					
Reflex	341.00	11.30°	-56.20°	Non					
Reflex	344.00	11.30°	-56.10°	Non					
Reflex	347.00	11.30°	-56.00°	Non					
Reflex	350.00	11.30°	-56.00°	Non					
Reflex	353.00	11.20°	-55.80°	Non					
Reflex	356.00	11.30°	-55.90°	Non					
Reflex	359.00	11.30°	-55.80°	Non					
Reflex	362.00	11.40°	-55.70°	Non					
Reflex	365.00	11.50°	-55.70°	Non					
Reflex	368.00	11.40°	-55.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.10	MT						
		<b>Mort-terrain</b>						
0.10	327.00	SY; POR	0.10	1.50	D012821	1.40	<0.005	0.001
		<b>Syénite; Porphyrique</b>	1.50	3.00	D012822	1.50	<0.005	0.001
		Phorphyritic syenite. Carbonate and hematite alteration. Magnetic.	3.00	4.50	D012823	1.50	<0.005	0.001
			4.50	6.00	D012824	1.50	<0.005	0.001
			6.00	7.50	D012826	1.50	<0.005	0.001
			7.50	9.00	D012827	1.50	<0.005	0.001
			9.00	10.50	D012828	1.50	<0.005	0.001
			10.50	12.00	D012829	1.50	0.007	0.007
			12.00	13.50	D012830	1.50	0.010	0.010
			13.50	15.00	D012831	1.50	<0.005	0.001
			15.00	16.50	D012832	1.50	0.054	0.054
			16.50	18.00	D012833	1.50	0.092	0.092
			18.00	19.50	D012834	1.50	<0.005	0.001
			19.50	21.00	D012836	1.50	<0.005	0.001
			21.00	22.50	D012837	1.50	<0.005	0.001
			22.50	24.00	D012838	1.50	<0.005	0.001
			24.00	25.50	D012839	1.50	<0.005	0.001
			25.50	27.00	D012841	1.50	<0.005	0.001
			27.00	28.50	D012842	1.50	<0.005	0.001
			28.50	30.00	D012843	1.50	<0.005	0.001
			30.00	31.50	D012844	1.50	<0.005	0.001
			31.50	33.00	D012846	1.50	<0.005	0.001
			33.00	34.50	D012847	1.50	<0.005	0.001
			34.50	36.00	D012848	1.50	<0.005	0.001
			36.00	37.50	D012849	1.50	<0.005	0.001
			37.50	39.00	D012850	1.50	<0.005	0.001
			39.00	40.50	D012851	1.50	<0.005	0.001
			40.50	42.00	D012852	1.50	<0.005	0.001
			42.00	43.50	D012853	1.50	<0.005	0.001
			43.50	45.00	D012854	1.50	<0.005	0.001
			45.00	46.50	D012856	1.50	0.011	0.011
			46.50	48.00	D012857	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.00	49.50	D012858	1.50	<0.005		0.001
	49.50	51.00	D012859	1.50	<0.005		0.001
	51.00	52.50	D012860	1.50	<0.005		0.001
	52.50	54.00	D012861	1.50	<0.005		0.001
	54.00	55.50	D012862	1.50	<0.005		0.001
	55.50	57.00	D012863	1.50	<0.005		0.001
	57.00	58.50	D012864	1.50	<0.005		0.001
	58.50	60.00	D012866	1.50	<0.005		0.001
	60.00	61.50	D012867	1.50	<0.005		0.001
	61.50	63.00	D012868	1.50	<0.005		0.001
	63.00	64.50	D012869	1.50	<0.005		0.001
	64.50	66.00	D012870	1.50	<0.005		0.001
	66.00	67.50	D012871	1.50	<0.005		0.001
	67.50	69.00	D012872	1.50	0.005		0.005
	69.00	70.00	D012873	1.00	0.024		0.024
	70.00	71.50	D012874	1.50	<0.005		0.001
	71.50	73.00	D012876	1.50	<0.005		0.001
	73.00	74.60	D012877	1.60	0.018		0.018
	74.60	76.00	D012878	1.40	0.030		0.030
	76.00	77.50	D012879	1.50	0.014		0.014
	77.50	79.00	D012881	1.50	<0.005		0.001
	79.00	80.50	D012882	1.50	<0.005		0.001
	80.50	82.00	D012883	1.50	0.005		0.005
	82.00	83.60	D012884	1.60	0.013		0.013
	83.60	85.00	D012886	1.40	0.074		0.074
	85.00	86.50	D012887	1.50	<0.005		0.001
	86.50	88.00	D012888	1.50	<0.005		0.001
	88.00	89.50	D012889	1.50	<0.005		0.001
	89.50	91.00	D012890	1.50	<0.005		0.001
	91.00	92.50	D012891	1.50	0.008		0.008
	92.50	94.00	D012892	1.50	0.013		0.013
	94.00	95.50	D012893	1.50	<0.005		0.001
	95.50	97.00	D012894	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	97.00	98.70	D012896	1.70	0.102		0.102
	98.70	100.00	D012897	1.30	<0.005		0.001
	100.00	101.10	D012898	1.10	<0.005		0.001
	101.10	102.30	D012899	1.20	<0.005		0.001
	102.30	104.00	D012900	1.70	0.019		0.019
	104.00	105.00	D012901	1.00	0.049		0.049
	105.00	106.50	D012902	1.50	0.202		0.202
	106.50	108.00	D012903	1.50	0.007		0.007
	108.00	109.50	D012904	1.50	0.077		0.077
	109.50	111.00	D012906	1.50	0.236		0.236
	111.00	112.50	D012907	1.50	0.016		0.016
	112.50	114.00	D012908	1.50	0.025		0.025
	114.00	115.50	D012909	1.50	0.066		0.066
	115.50	117.00	D012910	1.50	<0.005		0.001
	117.00	118.00	D012911	1.00	0.005		0.005
	118.00	119.50	D012912	1.50	0.084		0.084
	119.50	121.00	D012913	1.50	0.044		0.044
	121.00	122.50	D012914	1.50	0.006		0.006
	122.50	124.00	D012916	1.50	0.082		0.082
	124.00	125.50	D012917	1.50	0.005		0.005
	125.50	127.00	D012918	1.50	0.005		0.005
	127.00	128.50	D012919	1.50	0.016		0.016
	128.50	130.00	D012921	1.50	0.022		0.022
	130.00	131.50	D012922	1.50	0.005		0.005
	131.50	133.00	D012923	1.50	0.141		0.141
	133.00	134.50	D012924	1.50	0.007		0.007
	134.50	136.00	D012926	1.50	<0.005		0.001
	136.00	137.50	D012927	1.50	<0.005		0.001
	137.50	139.00	D012928	1.50	0.054		0.054
	139.00	140.50	D012929	1.50	0.602		0.602
	140.50	142.00	D012930	1.50	0.006		0.006
	142.00	143.50	D012931	1.50	0.005		0.005
	143.50	145.00	D012932	1.50	0.012		0.012

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	145.00	146.50	D012933	1.50	0.166		0.166
	146.50	148.00	D012934	1.50	0.520		0.520
	148.00	149.50	D012936	1.50	0.267		0.267
	149.50	151.00	D012937	1.50	0.005		0.005
	151.00	152.50	D012938	1.50	0.008		0.008
	152.50	154.00	D012939	1.50	0.012		0.012
	154.00	155.50	D012940	1.50	0.006		0.006
	155.50	157.00	D012941	1.50	<0.005		0.001
	157.00	158.50	D012942	1.50	<0.005		0.001
	158.50	160.00	D012943	1.50	<0.005		0.001
	160.00	161.50	D012944	1.50	<0.005		0.001
	161.50	163.00	D012946	1.50	<0.005		0.001
	163.00	164.50	D012947	1.50	0.357		0.357
	164.50	166.00	D012948	1.50	0.669		0.669
	166.00	167.50	D012949	1.50	0.059		0.059
	167.50	169.00	D012950	1.50	0.020		0.020
	169.00	170.50	D012951	1.50	0.005		0.005
	170.50	172.00	D012952	1.50	0.008		0.008
	172.00	173.50	D012953	1.50	<0.005		0.001
	173.50	175.00	D012954	1.50	0.005		0.005
	175.00	176.50	D012956	1.50	0.293		0.293
	176.50	178.00	D012957	1.50	0.035		0.035
	178.00	179.50	D012958	1.50	0.069		0.069
	179.50	181.00	D012959	1.50	<0.005		0.001
	181.00	182.50	D012961	1.50	0.029		0.029
	182.50	184.00	D012962	1.50	<0.005		0.001
	184.00	185.50	D012963	1.50	<0.005		0.001
	185.50	187.00	D012964	1.50	0.329		0.329
	187.00	188.50	D012966	1.50	<0.005		0.001
	188.50	190.00	D012967	1.50	<0.005		0.001
	190.00	191.00	D012968	1.00	0.007		0.007
191.00	192.30	PT	D012969	1.30	0.068		0.068
		<b>Porphyre trachytique</b>	D012970	1.70	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	194.00	195.50	D012971	1.50	0.037		0.037	
	195.50	197.00	D012972	1.50	0.019		0.019	
	197.00	198.50	D012973	1.50	0.043		0.043	
	198.50	200.00	D012974	1.50	0.015		0.015	
	200.00	201.50	D012976	1.50	0.209		0.209	
	201.50	203.00	D012977	1.50	0.012		0.012	
	203.00	204.50	D012978	1.50	<0.005		0.001	
	204.50	206.00	D012979	1.50	0.033		0.033	
	206.00	207.50	D012980	1.50	<0.005		0.001	
	207.50	209.00	D012981	1.50	0.006		0.006	
	209.00	210.50	D012982	1.50	<0.005		0.001	
	210.50	212.00	D012983	1.50	<0.005		0.001	
	212.00	213.50	D012984	1.50	0.005		0.005	
	213.50	215.00	D012986	1.50	<0.005		0.001	
	215.00	216.50	D012987	1.50	<0.005		0.001	
	216.50	218.00	D012988	1.50	<0.005		0.001	
	218.00	219.50	D012989	1.50	<0.005		0.001	
	219.50	221.00	D012990	1.50	0.051		0.051	
	221.00	222.50	D012991	1.50	<0.005		0.001	
	222.50	224.00	D012992	1.50	<0.005		0.001	
	224.00	225.50	D012993	1.50	<0.005		0.001	
	225.50	227.00	D012994	1.50	<0.005		0.001	
	227.00	228.50	D012996	1.50	<0.005		0.001	
	228.50	230.00	D012997	1.50	0.008		0.008	
	230.00	231.50	D012998	1.50	<0.005		0.001	
	231.50	232.90	D012999	1.40	<0.005		0.001	
	232.90	233.90	D013001	1.00	<0.005		0.001	
233.90	239.50	PT	233.90	235.50	D013002	1.60	<0.005	0.001
		<b>Porphyre trachytique</b>	235.50	237.00	D013003	1.50	<0.005	0.001
			237.00	238.20	D013004	1.20	<0.005	0.001
			238.20	239.70	D013006	1.50	0.257	0.257
			239.70	241.00	D013007	1.30	1.025	1.025
			241.00	242.00	D013008	1.00	0.202	0.202

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	242.00	243.50	D013009	1.50	0.094		0.094
	243.50	245.00	D013010	1.50	0.065		0.065
	245.00	246.50	D013011	1.50	0.215		0.215
	246.50	248.00	D013012	1.50	0.018		0.018
	248.00	249.50	D013013	1.50	0.030		0.030
	249.50	251.00	D013014	1.50	0.023		0.023
	251.00	252.50	D013016	1.50	<0.005		0.001
	252.50	254.00	D013017	1.50	0.018		0.018
	254.00	255.50	D013018	1.50	<0.005		0.001
	255.50	257.00	D013019	1.50	0.013		0.013
	257.00	258.50	D013020	1.50	0.020		0.020
	258.50	260.00	D013021	1.50	<0.005		0.001
	260.00	261.50	D013022	1.50	0.008		0.008
	261.50	263.00	D013023	1.50	0.832		0.832
	263.00	264.50	D013024	1.50	0.005		0.005
	264.50	266.00	D013026	1.50	<0.005		0.001
	266.00	267.50	D013027	1.50	<0.005		0.001
	267.50	269.00	D013028	1.50	<0.005		0.001
	269.00	270.50	D013029	1.50	0.012		0.012
	270.50	272.00	D013030	1.50	0.005		0.005
	272.00	273.50	D013031	1.50	<0.005		0.001
	273.50	275.00	D013032	1.50	<0.005		0.001
	275.00	276.50	D013033	1.50	<0.005		0.001
	276.50	278.00	D013034	1.50	0.006		0.006
	278.00	279.50	D013036	1.50	0.477		0.477
	279.50	281.00	D013037	1.50	0.124		0.124
	281.00	282.50	D013038	1.50	0.015		0.015
	282.50	284.00	D013039	1.50	0.022		0.022
	284.00	285.50	D013041	1.50	0.005		0.005
	285.50	287.00	D013042	1.50	<0.005		0.001
	287.00	288.00	D013043	1.00	0.017		0.017
	288.00	289.50	D013044	1.50	0.108		0.108
	289.50	291.00	D013046	1.50	0.286		0.286

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			291.00	292.50	D013047	1.50		0.064	0.064
			292.50	294.00	D013048	1.50		<0.005	0.001
			294.00	295.50	D013049	1.50		0.018	0.018
			295.50	297.00	D013050	1.50		0.015	0.015
			297.00	298.50	D013051	1.50		0.019	0.019
			298.50	300.00	D013052	1.50		0.167	0.167
			300.00	301.50	D013053	1.50		0.124	0.124
			301.50	303.00	D013054	1.50		0.020	0.020
			303.00	304.50	D013056	1.50		0.025	0.025
			304.50	306.00	D013057	1.50		0.107	0.107
			306.00	307.50	D013058	1.50		0.094	0.094
			307.50	309.00	D013059	1.50		0.608	0.608
			309.00	310.50	D013060	1.50		0.092	0.092
			310.50	312.00	D013061	1.50		0.009	0.009
			312.00	313.00	D013062	1.00		0.011	0.011
			313.00	314.10	D013063	1.10		0.024	0.024
			314.10	315.80	D013064	1.70		0.030	0.030
			315.80	317.50	D013066	1.70		0.038	0.038
			317.50	318.40	D013067	0.90		3.750	3.750
			320.00	321.50	D013068	1.50		2.810	2.810
			321.50	323.00	D013069	1.50		1.915	1.915
			323.00	324.50	D013070	1.50		2.480	2.480
			324.50	326.00	D013071	1.50		2.660	2.660
			326.00	327.00	D013072	1.00		0.389	0.389
327.00	361.10	BA	327.00	328.50	D013073	1.50		<0.005	0.001
		<b>Basalte</b>	328.50	330.00	D013074	1.50		<0.005	0.001
		Amygdalaire basalt. Carbonate alteration.	330.00	331.50	D013076	1.50		<0.005	0.001
			331.50	333.00	D013077	1.50		<0.005	0.001
			333.00	334.50	D013078	1.50		<0.005	0.001
			334.50	336.00	D013079	1.50		<0.005	0.001
			336.00	337.50	D013081	1.50		<0.005	0.001
			337.50	339.00	D013082	1.50		<0.005	0.001
			339.00	340.50	D013083	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			340.50	342.00	D013084	1.50	<0.005		0.001
			342.00	343.50	D013086	1.50	<0.005		0.001
			343.50	345.00	D013087	1.50	<0.005		0.001
			345.00	346.50	D013088	1.50	<0.005		0.001
			346.50	348.00	D013089	1.50	<0.005		0.001
			348.00	349.50	D013090	1.50	<0.005		0.001
			349.50	351.00	D013091	1.50	<0.005		0.001
			351.00	352.50	D013092	1.50	<0.005		0.001
			352.50	354.00	D013093	1.50	<0.005		0.001
			354.00	355.50	D013094	1.50	<0.005		0.001
			355.50	357.00	D013096	1.50	<0.005		0.001
			357.00	358.50	D013097	1.50	<0.005		0.001
			358.50	360.00	D013098	1.50	<0.005		0.001
			360.00	361.10	D013099	1.10	<0.005		0.001
361.10	366.60	ST <b>Siltstone 25°</b>	361.10	362.80	D013100	1.70	<0.005		0.001
			362.80	364.50	D013101	1.70	<0.005		0.001
			364.50	365.50	D013102	1.00	<0.005		0.001
			365.50	366.60	D013103	1.10	0.005		0.005
366.60	373.70	BA; AMY <b>Basalte 15°; Amygdalaire</b> Amygdalaire Basalte interlayered with graphitic sediments.	366.60	368.00	D013104	1.40	<0.005		0.001
			368.00	369.50	D013106	1.50	<0.005		0.001
			369.50	371.00	D013107	1.50	<0.005		0.001
			371.00	372.50	D013108	1.50	<0.005		0.001
			372.50	373.70	D013109	1.20	<0.005		0.001
373.70	394.50	ST <b>Siltstone 15°</b> Massive siltstone, fine to coarse grained. Intermittent layers of graphite rich sediments.	373.70	375.00	D013110	1.30	<0.005		0.001
			375.00	376.50	D013111	1.50	<0.005		0.001
			376.50	378.00	D013112	1.50	<0.005		0.001
			378.00	379.50	D013113	1.50	<0.005		0.001
			379.50	381.00	D013114	1.50	<0.005		0.001
			381.00	382.50	D013116	1.50	<0.005		0.001
			382.50	384.00	D013117	1.50	<0.005		0.001
			384.00	385.50	D013118	1.50	<0.005		0.001
			385.50	387.00	D013119	1.50	<0.005		0.001
			387.00	388.50	D013121	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
394.50	413.00	BA; AMY <b>Basalte 15°; Amygdalaire</b> Amygdalaire Basalte interlayered with graphitic sediments.	388.50	390.00	D013122	1.50	<0.005		0.001
			390.00	391.50	D013123	1.50	<0.005		0.001
			391.50	393.00	D013124	1.50	<0.005		0.001
			393.00	394.50	D013126	1.50	<0.005		0.001
			394.50	396.00	D013127	1.50	<0.005		0.001
			396.00	397.50	D013128	1.50	0.007		0.007
			397.50	399.00	D013129	1.50	<0.005		0.001
			399.00	400.50	D013130	1.50	0.007		0.007
			400.50	402.00	D013131	1.50	<0.005		0.001
			402.00	403.50	D013132	1.50	<0.005		0.001
			403.50	405.00	D013133	1.50	<0.005		0.001
			405.00	406.50	D013134	1.50	<0.005		0.001
			406.50	408.00	D013136	1.50	<0.005		0.001
			408.00	409.50	D013137	1.50	<0.005		0.001
			409.50	411.00	D013138	1.50	<0.005		0.001
			411.00	412.00	D013139	1.00	<0.005		0.001
			412.00	413.00	D013140	1.00	<0.005		0.001
413.00	Fin du sondage Nombre d'échantillons : 280 Nombre d'échantillons QAQC : 40 Longueur totale échantillonnée : 411.30								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.50	6.00	D012825	D012824	1.50	<0.005	0.001
18.00	18.00	D012835	H	0.00	0.927	0.927
24.00	24.00	D012840	M1	0.00	<0.005	0.001
30.00	31.50	D012845	D012844	1.50	<0.005	0.001
43.50	43.50	D012855	A3	0.00	0.621	0.621
57.00	58.50	D012865	D012864	1.50	<0.005	0.001
70.00	70.00	D012875	B4	0.00	2.590	2.590
76.00	76.00	D012880	M1	0.00	<0.005	0.001
82.00	83.60	D012885	D012884	1.60	0.007	0.007
95.50	95.50	D012895	C4	0.00	1.390	1.390
108.00	109.50	D012905	D012904	1.50	0.050	0.050
121.00	121.00	D012915	D2	0.00	0.784	0.784
127.00	127.00	D012920	M1	0.00	<0.005	0.001
133.00	134.50	D012925	D012924	1.50	0.005	0.005
146.50	146.50	D012935	F2	0.00	8.460	8.460
160.00	161.50	D012945	D012944	1.50	<0.005	0.001
173.50	173.50	D012955	H	0.00	0.658	0.658
179.50	179.50	D012960	M1	0.00	<0.005	0.001
185.50	187.00	D012965	D012964	1.50	0.164	0.164
198.50	198.50	D012975	A3	0.00	0.610	0.610
212.00	213.50	D012985	D012984	1.50	0.005	0.005
225.50	225.50	D012995	B4	0.00	2.560	2.560
231.50	231.50	D013000	M1	0.00	<0.005	0.001
237.00	238.20	D013005	D013004	1.20	0.006	0.006
249.50	249.50	D013015	C4	0.00	1.335	1.335
263.00	264.50	D013025	D013024	1.50	<0.005	0.001
276.50	276.50	D013035	D2	0.00	0.838	0.838
282.50	282.50	D013040	M1	0.00	<0.005	0.001
288.00	289.50	D013045	D013044	1.50	0.187	0.187
301.50	301.50	D013055	F2	0.00	8.670	8.670
314.10	315.80	D013065	D013064	1.70	0.027	0.027
328.50	328.50	D013075	H	0.00	0.972	0.972
334.50	334.50	D013080	M1	0.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
340.50	342.00	D013085	D013084	1.50	<0.005	0.001
354.00	354.00	D013095	A3	0.00	0.508	0.508
366.60	368.00	D013105	D013104	1.40	<0.005	0.001
380.00	380.00	D013115	B4	0.00	2.580	2.580
386.00	386.00	D013120	M1	0.00	<0.005	0.001
391.50	393.00	D013125	D013124	1.50	0.017	0.017
405.00	405.00	D013135	C4	0.00	1.370	1.370

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-157</b>	Titre minier :	Section :	630 800
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles. KAMTA	Du : 2010-04-13	Date de description :	2010-05-08
	Au : 2010-04-17		

Collet

Azimut : 180.00°  
 Plongée : -60.00°  
 Longueur : 473.00 m

UTM

Est	630 799.8
Nord	5 374 449.7
Élévation	314.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	170.30°	-58.90°	Oui
Reflex	5.00	186.00°	-59.50°	Oui
Reflex	8.00	182.50°	-59.00°	Oui
Reflex	11.00	180.50°	-59.10°	Non
Reflex	14.00	181.50°	-59.10°	Non
Reflex	17.00	181.90°	-59.10°	Non
Reflex	20.00	183.00°	-59.20°	Oui
Reflex	23.00	181.30°	-59.20°	Non
Reflex	26.00	182.60°	-59.10°	Non
Reflex	29.00	182.80°	-59.10°	Non
Reflex	32.00	183.30°	-59.10°	Non
Reflex	35.00	184.10°	-58.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	182.30°	-58.80°	Non
Reflex	41.00	183.00°	-58.90°	Non
Reflex	44.00	182.60°	-58.90°	Non
Reflex	47.00	182.50°	-59.00°	Non
Reflex	50.00	182.40°	-58.90°	Non
Reflex	53.00	182.60°	-59.00°	Non
Reflex	56.00	182.30°	-59.00°	Non
Reflex	59.00	184.00°	-59.00°	Non
Reflex	62.00	185.80°	-59.00°	Non
Reflex	65.00	183.70°	-59.00°	Non
Reflex	68.00	184.80°	-59.00°	Non
Reflex	71.00	185.10°	-59.10°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	184.80°	-59.10°	Non
Reflex	77.00	184.20°	-59.10°	Non
Reflex	80.00	185.00°	-59.10°	Non
Reflex	83.00	184.70°	-59.20°	Non
Reflex	86.00	185.90°	-59.20°	Non
Reflex	89.00	185.20°	-59.20°	Non
Reflex	92.00	185.70°	-59.20°	Non
Reflex	95.00	185.30°	-59.20°	Non
Reflex	98.00	184.10°	-59.30°	Non
Reflex	101.00	186.50°	-59.30°	Non
Reflex	104.00	186.60°	-59.30°	Non
Reflex	107.00	188.00°	-59.30°	Oui
Reflex	110.00	186.80°	-59.20°	Non
Reflex	113.00	188.30°	-59.40°	Oui
Reflex	116.00	187.80°	-59.30°	Non
Reflex	119.00	187.80°	-59.30°	Non
Reflex	122.00	187.60°	-59.40°	Non
Reflex	125.00	187.60°	-59.30°	Non
Reflex	128.00	187.70°	-59.40°	Non
Reflex	131.00	187.90°	-59.30°	Non
Reflex	134.00	187.90°	-59.40°	Non
Reflex	137.00	188.00°	-59.40°	Non
Reflex	140.00	187.90°	-59.40°	Non
Reflex	143.00	188.10°	-59.40°	Non
Reflex	146.00	188.10°	-59.50°	Non
Reflex	149.00	188.30°	-59.50°	Non
Reflex	152.00	188.40°	-59.50°	Non
Reflex	155.00	188.50°	-59.40°	Non
Reflex	158.00	188.40°	-59.40°	Non
Reflex	161.00	188.00°	-59.50°	Non
Reflex	164.00	188.20°	-59.50°	Non
Reflex	167.00	187.90°	-59.40°	Non
Reflex	170.00	187.90°	-59.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	187.20°	-59.50°	Non
Reflex	176.00	187.50°	-59.50°	Non
Reflex	179.00	188.70°	-59.60°	Non
Reflex	182.00	189.10°	-59.60°	Non
Reflex	185.00	189.40°	-59.60°	Non
Reflex	188.00	189.20°	-59.60°	Non
Reflex	191.00	189.50°	-59.60°	Non
Reflex	194.00	189.30°	-59.70°	Non
Reflex	197.00	189.80°	-59.60°	Non
Reflex	200.00	190.40°	-59.60°	Non
Reflex	203.00	190.20°	-59.70°	Non
Reflex	206.00	188.30°	-59.70°	Non
Reflex	209.00	189.40°	-59.70°	Non
Reflex	212.00	190.50°	-59.70°	Non
Reflex	215.00	190.50°	-59.70°	Non
Reflex	218.00	190.00°	-59.70°	Non
Reflex	221.00	190.30°	-59.70°	Non
Reflex	224.00	190.30°	-59.70°	Non
Reflex	227.00	190.60°	-59.70°	Non
Reflex	230.00	190.70°	-59.70°	Non
Reflex	233.00	191.20°	-59.80°	Non
Reflex	236.00	191.10°	-59.80°	Non
Reflex	239.00	191.40°	-59.80°	Non
Reflex	242.00	191.70°	-59.80°	Non
Reflex	245.00	191.60°	-59.80°	Non
Reflex	248.00	191.90°	-59.80°	Non
Reflex	251.00	192.20°	-59.80°	Non
Reflex	254.00	192.00°	-59.80°	Non
Reflex	257.00	192.10°	-59.80°	Non
Reflex	260.00	191.40°	-59.70°	Non
Reflex	263.00	192.00°	-59.80°	Non
Reflex	266.00	192.10°	-59.80°	Non
Reflex	269.00	192.30°	-59.80°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	192.10°	-59.80°	Non	Reflex	371.00	191.70°	-59.30°	Non
Reflex	275.00	192.20°	-59.70°	Non	Reflex	374.00	193.60°	-59.40°	Non
Reflex	278.00	192.20°	-59.70°	Non	Reflex	377.00	193.20°	-59.40°	Non
Reflex	281.00	192.30°	-59.80°	Non	Reflex	380.00	193.00°	-59.40°	Non
Reflex	284.00	192.50°	-59.70°	Non	Reflex	383.00	193.40°	-59.30°	Non
Reflex	287.00	192.50°	-59.80°	Non	Reflex	386.00	192.00°	-59.40°	Non
Reflex	290.00	192.20°	-59.80°	Non	Reflex	389.00	194.00°	-59.40°	Non
Reflex	293.00	191.80°	-59.80°	Non	Reflex	392.00	195.00°	-59.30°	Non
Reflex	296.00	192.10°	-59.80°	Non	Reflex	395.00	194.60°	-59.30°	Non
Reflex	299.00	191.70°	-59.80°	Non	Reflex	398.00	194.50°	-59.30°	Non
Reflex	302.00	191.80°	-59.80°	Non	Reflex	401.00	195.60°	-59.30°	Non
Reflex	305.00	191.80°	-59.80°	Non	Reflex	404.00	194.70°	-59.30°	Non
Reflex	308.00	191.80°	-59.80°	Non	Reflex	407.00	194.50°	-59.30°	Non
Reflex	311.00	191.30°	-59.80°	Non	Reflex	410.00	195.20°	-59.30°	Non
Reflex	314.00	191.50°	-59.80°	Non	Reflex	413.00	195.10°	-59.30°	Non
Reflex	317.00	191.80°	-59.80°	Non	Reflex	416.00	195.50°	-59.30°	Non
Reflex	320.00	191.70°	-59.80°	Non	Reflex	419.00	195.00°	-59.30°	Non
Reflex	323.00	191.90°	-59.80°	Non	Reflex	422.00	194.90°	-59.20°	Non
Reflex	326.00	192.60°	-59.70°	Non	Reflex	425.00	199.50°	-59.30°	Oui
Reflex	329.00	192.30°	-59.70°	Non	Reflex	428.00	194.80°	-59.30°	Non
Reflex	332.00	192.80°	-59.70°	Non	Reflex	431.00	193.60°	-59.30°	Non
Reflex	335.00	192.80°	-59.60°	Non	Reflex	434.00	194.80°	-59.20°	Non
Reflex	338.00	193.00°	-59.60°	Non	Reflex	437.00	192.90°	-59.20°	Non
Reflex	341.00	193.00°	-59.60°	Non	Reflex	440.00	193.80°	-59.20°	Non
Reflex	344.00	193.50°	-59.60°	Non	Reflex	443.00	194.30°	-59.30°	Non
Reflex	347.00	192.80°	-59.60°	Non	Reflex	446.00	195.10°	-59.30°	Non
Reflex	350.00	192.70°	-59.50°	Non	Reflex	449.00	194.20°	-59.30°	Non
Reflex	353.00	193.20°	-59.50°	Non	Reflex	452.00	194.70°	-59.30°	Non
Reflex	356.00	192.90°	-59.50°	Non	Reflex	455.00	195.40°	-59.30°	Non
Reflex	359.00	193.50°	-59.50°	Non	Reflex	458.00	195.60°	-59.30°	Non
Reflex	362.00	193.10°	-59.40°	Non	Reflex	461.00	194.50°	-59.30°	Non
Reflex	365.00	193.10°	-59.40°	Non	Reflex	464.00	194.90°	-59.30°	Non
Reflex	368.00	193.30°	-59.40°	Non	Reflex	467.00	195.30°	-59.20°	Non



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.60	MT						
		<b>Mort-terrain</b>						
0.60	29.50	SY; FIN; MAS	0.60	2.00	D002801	1.40	<0.005	0.001
		<b>Syénite; Grains fins; Roche massive</b>						
		grenue, altération en calcite, hématisation, localement oxyde de carbonates, veines de QZ carbonaté, cheveux carbonaté, SR+, BO+, CL++, PY fine diss	2.00	3.50	D002802	1.50	<0.005	0.001
			3.50	5.00	D002803	1.50	<0.005	0.001
			5.00	6.50	D002804	1.50	<0.005	0.001
			6.50	8.00	D002805	1.50	<0.005	0.001
			8.00	9.50	D002806	1.50	<0.005	0.001
			9.50	11.00	D002807	1.50	0.008	0.008
			11.00	12.50	D002808	1.50	0.013	0.013
			12.50	14.00	D002809	1.50	<0.005	0.001
			14.00	15.50	D002811	1.50	0.006	0.006
			15.50	17.00	D002812	1.50	0.013	0.013
			17.00	18.50	D002813	1.50	<0.005	0.001
			18.50	20.00	D002814	1.50	<0.005	0.001
			20.00	21.20	D002815	1.20	<0.005	0.001
			21.20	22.20	D002816	1.00	<0.005	0.001
			22.20	23.80	D002817	1.60	<0.005	0.001
			23.80	25.00	D002818	1.20	<0.005	0.001
			25.00	26.50	D002819	1.50	0.039	0.039
			26.50	28.00	D002821	1.50	0.527	0.527
			28.00	29.50	D002822	1.50	0.018	0.018
0.60	15.50	SY; POR						
		<b>Syénite; Porphyrique</b>						
		phénocristaux de FP automorphe à sub automorphe 0.2-2 cm, fortement altéré en calcite, hématisation, BO++						
29.50	29.80	NR						
		<b>Carotte perdue</b>						
29.80	261.30	SY; FIN; MAS	29.80	31.00	D002823	1.20	<0.005	0.001
		<b>Syénite; Grains fins; Roche massive</b>						
		grenue, localement phénocristaux automorphe à sub automorphe 1-2%, veines, veinules et cheveux de QZ et/ou carbonates, oxydes de carbonates ocre, localement calcique, hématisé, passage séricitisé, PY fine irrég diss						
30.00	44.50	SY; POR	31.00	32.50	D002824	1.50	0.005	0.005
		<b>Syénite; Porphyrique</b>						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
46.50	74.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux 0.2-2 cm, altération en calcite, hématisation, HM+++; PY fine irrég diss	32.50	34.00	D002825	1.50	<0.005		0.001
			34.00	35.50	D002826	1.50	<0.005		0.001
			35.50	37.00	D002827	1.50	<0.005		0.001
			37.00	38.50	D002828	1.50	0.007		0.007
			38.50	40.00	D002829	1.50	0.005		0.005
			40.00	41.50	D002831	1.50	0.005		0.005
			41.50	43.00	D002832	1.50	0.005		0.005
			43.00	44.50	D002833	1.50	<0.005		0.001
			44.50	45.50	D002834	1.00	0.116		0.116
			45.50	46.50	D002835	1.00	0.023		0.023
			46.50	48.00	D002836	1.50	0.005		0.005
			48.00	49.50	D002838	1.50	<0.005		0.001
			49.50	51.00	D002839	1.50	0.177		0.177
			51.00	52.50	D002841	1.50	0.048		0.048
			52.50	54.00	D002842	1.50	0.214		0.214
			54.00	55.50	D002843	1.50	0.007		0.007
			77.50	117.20	SY; POR <b>Syénite; Porphyrique</b> phénocristaux 4-10%, 0.2-2 cm zonée, veines de QZ carbonaté hématisation et légère séricitisation	55.50	57.00	D002844	1.50
57.00	58.50	D002845				1.50	0.036		0.036
58.50	60.00	D002846				1.50	0.027		0.027
60.00	61.50	D002847				1.50	0.005		0.005
61.50	63.00	D002848				1.50	0.038		0.038
63.00	64.50	D002849				1.50	0.014		0.014
64.50	66.00	D002851				1.50	0.007		0.007
66.00	67.50	D002852				1.50	<0.005		0.001
67.50	68.50	D002853				1.00	0.007		0.007
68.50	70.00	D002854				1.50	0.007		0.007
70.00	71.50	D002855				1.50	0.016		0.016
71.50	73.00	D002856				1.50	0.039		0.039
73.00	74.50	D002857				1.50	0.015		0.015
74.50	76.00	D002858				1.50	0.053		0.053
76.00	77.50	D002859				1.50	0.118		0.118
77.50	79.00	D002861				1.50	0.009		0.009
79.00	80.50	D002862				1.50	0.074		0.074

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
séricitisé, fortement hématisé, +calcite	80.50	82.00	D002863	1.50	0.024		0.024
	82.00	83.50	D002864	1.50	0.042		0.042
	83.50	85.00	D002865	1.50	0.012		0.012
	85.00	86.50	D002866	1.50	<0.005		0.001
	86.50	88.00	D002867	1.50	<0.005		0.001
	88.00	89.50	D002868	1.50	0.005		0.005
	89.50	91.00	D002869	1.50	<0.005		0.001
	91.00	92.50	D002871	1.50	0.007		0.007
	92.50	94.00	D002872	1.50	0.008		0.008
	94.00	95.50	D002873	1.50	0.020		0.020
	95.50	97.00	D002874	1.50	<0.005		0.001
	97.00	98.50	D002875	1.50	<0.005		0.001
	98.50	100.00	D002876	1.50	<0.005		0.001
	100.00	101.50	D002878	1.50	0.013		0.013
	101.50	103.00	D002879	1.50	0.028		0.028
	103.00	104.50	D002881	1.50	0.032		0.032
	104.50	106.00	D002882	1.50	0.021		0.021
	106.00	107.50	D002883	1.50	0.008		0.008
	107.50	109.00	D002884	1.50	0.044		0.044
	109.00	110.50	D002885	1.50	1.960		1.960
	110.50	112.00	D002886	1.50	1.395		1.395
	112.00	113.50	D002887	1.50	0.931		0.931
	113.50	115.00	D002888	1.50	0.352		0.352
	115.00	116.50	D002889	1.50	0.437		0.437
	116.50	118.00	D002891	1.50	1.165		1.165
	118.00	119.50	D002892	1.50	0.190		0.190
	119.50	121.00	D002893	1.50	1.640		1.640
	121.00	122.50	D002894	1.50	0.090		0.090
122.50	124.00	D002895	1.50	0.034		0.034	
124.00	125.50	D002896	1.50	0.005		0.005	
125.50	126.60	D002897	1.10	0.019		0.019	
126.60	128.00	D002898	1.40	0.108		0.108	
128.00	129.50	D002899	1.50	0.021		0.021	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
143.50	149.70	SY; MOY; POR <b>Syénite 50°; Grains moyens; Porphyrique</b> syénite porphyrique à texture trachytique, phénocristaux 0.3-3 cm 30-40%, étiré et alignées 70-80° ac, BO+, SR+, +++calcite, PY fine diss	129.50	131.00	D002901	1.50	<0.005		0.001
			131.00	132.50	D002902	1.50	<0.005		0.001
			132.50	134.00	D002903	1.50	0.006		0.006
			134.00	135.50	D002904	1.50	0.006		0.006
			135.50	137.00	D002905	1.50	0.030		0.030
			137.00	138.50	D002906	1.50	1.100		1.100
			138.50	140.00	D002907	1.50	2.960		2.960
			140.00	141.50	D002908	1.50	0.066		0.066
			141.50	142.50	D002909	1.00	1.400		1.400
			142.50	143.50	D002911	1.00	0.614		0.614
			143.50	145.00	D002912	1.50	3.390		3.390
			145.00	146.50	D002913	1.50	4.850		4.850
			146.50	148.00	D002914	1.50	0.834		0.834
			148.00	149.70	D002915	1.70	0.951		0.951
			149.70	151.00	D002916	1.30	0.013		0.013
			151.00	152.50	D002918	1.50	0.005		0.005
			157.00	203.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe ou sub arrondi 0.2-2 cm altération en calcite, hématisation, SR+, PY fine irrég diss	152.50	154.00	D002919	1.50
154.00	155.50	D002921				1.50	0.008		0.008
155.50	157.00	D002922				1.50	0.009		0.009
157.00	158.50	D002923				1.50	0.008		0.008
158.50	160.00	D002924				1.50	0.007		0.007
160.00	161.50	D002925				1.50	0.005		0.005
161.50	163.00	D002926				1.50	<0.005		0.001
163.00	164.20	D002927				1.20	<0.005		0.001
164.20	165.50	D002928				1.30	0.035		0.035
165.50	167.00	D002929				1.50	0.021		0.021
167.00	168.50	D002931	1.50	0.095		0.095			
168.50	170.00	D002932	1.50	0.014		0.014			
170.00	171.50	D002933	1.50	0.269		0.269			
171.50	173.00	D002934	1.50	0.016		0.016			
173.00	174.50	D002935	1.50	<0.005		0.001			
174.50	176.00	D002936	1.50	<0.005		0.001			
176.00	177.50	D002937	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	177.50	179.00	D002938	1.50	0.501		0.501
	179.00	180.50	D002939	1.50	0.837		0.837
	180.50	182.00	D002941	1.50	<0.005		0.001
	182.00	183.50	D002942	1.50	<0.005		0.001
	183.50	185.00	D002943	1.50	<0.005		0.001
	185.00	186.50	D002944	1.50	<0.005		0.001
	186.50	188.00	D002945	1.50	<0.005		0.001
	188.00	189.50	D002946	1.50	<0.005		0.001
	189.50	191.00	D002947	1.50	<0.005		0.001
	191.00	192.50	D002948	1.50	0.007		0.007
	192.50	194.00	D002949	1.50	<0.005		0.001
	194.00	195.50	D002951	1.50	<0.005		0.001
	195.50	197.00	D002952	1.50	<0.005		0.001
	197.00	198.50	D002953	1.50	<0.005		0.001
	198.50	200.00	D002954	1.50	<0.005		0.001
	200.00	201.50	D002955	1.50	<0.005		0.001
	201.50	203.00	D002956	1.50	<0.005		0.001
	203.00	204.50	D002958	1.50	<0.005		0.001
	204.50	206.00	D002959	1.50	0.017		0.017
	206.00	207.50	D002961	1.50	<0.005		0.001
	207.50	209.00	D002962	1.50	<0.005		0.001
	209.00	210.50	D002963	1.50	<0.005		0.001
	210.50	212.00	D002964	1.50	<0.005		0.001
	212.00	213.50	D002965	1.50	<0.005		0.001
	213.50	215.00	D002966	1.50	<0.005		0.001
	215.00	216.50	D002967	1.50	<0.005		0.001
	216.50	218.00	D002968	1.50	<0.005		0.001
	218.00	219.50	D002969	1.50	<0.005		0.001
	219.50	221.00	D002971	1.50	<0.005		0.001
	221.00	222.50	D002972	1.50	0.008		0.008
	222.50	224.00	D002973	1.50	<0.005		0.001
	224.00	225.50	D002974	1.50	0.248		0.248
	225.50	227.00	D002975	1.50	0.942		0.942



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			227.00	228.50	D002976	1.50	<0.005		0.001
			228.50	230.00	D002977	1.50	<0.005		0.001
			230.00	231.50	D002978	1.50	<0.005		0.001
			231.50	233.00	D002979	1.50	<0.005		0.001
			233.00	234.50	D002981	1.50	<0.005		0.001
			234.50	236.00	D002982	1.50	<0.005		0.001
			236.00	237.50	D002983	1.50	<0.005		0.001
			237.50	239.00	D002984	1.50	<0.005		0.001
			239.00	240.50	D002985	1.50	0.074		0.074
			240.50	242.00	D002986	1.50	<0.005		0.001
			242.00	243.50	D002987	1.50	<0.005		0.001
			243.50	245.00	D002988	1.50	<0.005		0.001
			245.00	246.50	D002989	1.50	<0.005		0.001
			246.50	248.00	D002991	1.50	<0.005		0.001
			248.00	249.50	D002992	1.50	<0.005		0.001
			249.50	251.00	D002993	1.50	<0.005		0.001
			251.00	252.50	D002994	1.50	0.085		0.085
			252.50	254.00	D002995	1.50	0.006		0.006
			254.00	255.50	D002996	1.50	0.636		0.636
			255.50	257.00	D002998	1.50	1.435		1.435
			257.00	258.50	D002999	1.50	0.475		0.475
			258.50	260.00	D003001	1.50	0.209		0.209
			260.00	261.30	D003002	1.30	0.326		0.326
261.30	272.90	TU; FIN; MTY <b>Tuf à cendre/lapillis 40°; Grains fins; Grains moyens</b> granoclassé avec alternance de grains grossiers à fin, fragments felsiques mm sub arrondi ou étirés // cisaillement 30-40° ac, altération en séricite, chlorite, PY fine diss, passages de Syénite légèrement hématisé ± 20-30 cm							
			261.30	262.50	D003003	1.20	0.606		0.606
			262.50	264.00	D003004	1.50	0.095		0.095
			264.00	265.50	D003005	1.50	0.057		0.057
			265.50	267.00	D003006	1.50	<0.005		0.001
			267.00	268.50	D003007	1.50	0.189		0.189
261.30	272.90	CIS <b>Cisaillement 40°</b> cisaillement 20-50° ac, avec localement sub bréchifications							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
272.90	283.00	SY; POR <b>Syénite 50°; Porphyrique</b> syénite porphyrique fortement altéré en silice, lessivé, bréchifications à fragments mm- cm sub arrondi ou anguleux, localement fragment ± 3-4 cm bréchifié, légèrement hématisé et chloritisé, cheveux en réseaux, PY très fine diss	268.50	270.00	D003008	1.50	0.121		0.121
			270.00	271.50	D003009	1.50	0.813		0.813
			271.50	272.90	D003011	1.40	0.829		0.829
			272.90	274.50	D003012	1.60	7.650		7.650
			274.50	276.00	D003013	1.50	2.810		2.810
			276.00	277.50	D003014	1.50	2.830		2.830
			277.50	279.00	D003015	1.50	4.280		4.280
			279.00	280.50	D003016	1.50	4.030		4.030
			280.50	282.00	D003017	1.50	4.510		4.510
			282.00	283.00	D003018	1.00	5.250		5.250
283.00	473.00	SY; FIN <b>Syénite 20°; Grains fins</b> grains fin avec localement des phénocristaux de FP 1-3%, localement cisailé, veines et veinules de QZ et carbonâtes hématisé, séricitisation, chloritisation, hématisation, oxydes de carbonâtes, localement calcPY automorphe et fine irrég diss	283.00	284.50	D003019	1.50	0.523		0.523
			284.50	286.00	D003021	1.50	0.216		0.216
			286.00	287.50	D003022	1.50	0.284		0.284
			287.50	289.00	D003023	1.50	0.324		0.324
			289.00	290.50	D003024	1.50	0.101		0.101
			290.50	292.00	D003025	1.50	0.102		0.102
			292.00	293.50	D003026	1.50	0.209		0.209
			293.50	295.00	D003027	1.50	0.347		0.347
			295.00	296.50	D003028	1.50	0.275		0.275
			296.50	298.00	D003029	1.50	0.226		0.226
			298.00	299.50	D003031	1.50	0.443		0.443
			299.50	301.00	D003032	1.50	0.013		0.013
			301.00	302.50	D003033	1.50	0.030		0.030
			302.50	304.00	D003034	1.50	0.051		0.051
			304.00	305.50	D003035	1.50	0.019		0.019
			305.50	307.00	D003036	1.50	0.009		0.009
			307.00	308.50	D003038	1.50	0.048		0.048
308.50	310.00	D003039	1.50	0.033		0.033			
310.00	311.50	D003041	1.50	0.116		0.116			
311.50	313.00	D003042	1.50	0.009		0.009			
313.00	314.50	D003043	1.50	0.010		0.010			
314.50	316.00	D003044	1.50	0.049		0.049			
316.00	317.50	D003045	1.50	0.162		0.162			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	317.50	319.00	D003046	1.50	0.060		0.060
	319.00	320.50	D003047	1.50	0.018		0.018
	320.50	322.00	D003048	1.50	0.010		0.010
	322.00	323.50	D003049	1.50	0.027		0.027
	323.50	325.00	D003051	1.50	0.189		0.189
	325.00	326.50	D003052	1.50	0.056		0.056
	326.50	328.00	D003053	1.50	0.024		0.024
	328.00	329.50	D003054	1.50	0.011		0.011
	329.50	331.00	D003055	1.50	0.005		0.005
	331.00	332.50	D003056	1.50	0.006		0.006
	332.50	334.00	D003057	1.50	<0.005		0.001
	334.00	335.50	D003058	1.50	0.007		0.007
	335.50	337.00	D003059	1.50	0.045		0.045
	337.00	338.50	D003061	1.50	0.182		0.182
	338.50	340.00	D003062	1.50	0.109		0.109
	340.00	341.50	D003063	1.50	0.102		0.102
	341.50	343.00	D003064	1.50	0.095		0.095
	343.00	344.50	D003065	1.50	0.396		0.396
	344.50	346.00	D003066	1.50	0.007		0.007
	346.00	347.50	D003067	1.50	0.019		0.019
	347.50	349.00	D003068	1.50	0.044		0.044
	349.00	350.50	D003069	1.50	0.012		0.012
	350.50	352.00	D003071	1.50	<0.005		0.001
	352.00	353.50	D003072	1.50	0.009		0.009
	353.50	355.00	D003073	1.50	0.005		0.005
	355.00	356.50	D003074	1.50	0.049		0.049
	356.50	358.00	D003075	1.50	0.445		0.445
	358.00	359.50	D003076	1.50	0.108		0.108
	359.50	361.00	D003078	1.50	0.017		0.017
	361.00	362.50	D003079	1.50	0.036		0.036
	362.50	364.00	D003081	1.50	0.011		0.011
	364.00	365.50	D003082	1.50	0.054		0.054
	365.50	367.00	D003083	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	367.00	368.50	D003084	1.50	<0.005		0.001
	368.50	370.00	D003085	1.50	0.005		0.005
	370.00	371.50	D003086	1.50	0.005		0.005
	371.50	373.00	D003087	1.50	0.009		0.009
	373.00	374.50	D003088	1.50	0.012		0.012
	374.50	376.00	D003089	1.50	0.062		0.062
	376.00	377.50	D003091	1.50	0.005		0.005
	377.50	379.00	D003092	1.50	0.007		0.007
	379.00	380.50	D003093	1.50	0.114		0.114
	380.50	382.00	D003094	1.50	0.117		0.117
	382.00	383.50	D003095	1.50	<0.005		0.001
	383.50	385.00	D003096	1.50	<0.005		0.001
	385.00	386.50	D003097	1.50	<0.005		0.001
	386.50	388.00	D003098	1.50	<0.005		0.001
	388.00	389.50	D003099	1.50	<0.005		0.001
	389.50	391.00	D003101	1.50	<0.005		0.001
	391.00	392.50	D003102	1.50	<0.005		0.001
	392.50	394.00	D003103	1.50	0.005		0.005
	394.00	395.50	D003104	1.50	0.250		0.250
	395.50	397.00	D003105	1.50	0.301		0.301
	397.00	398.50	D003106	1.50	0.010		0.010
	398.50	400.00	D003107	1.50	<0.005		0.001
	400.00	401.50	D003108	1.50	<0.005		0.001
	401.50	403.00	D003109	1.50	<0.005		0.001
	403.00	404.50	D003111	1.50	<0.005		0.001
	404.50	406.00	D003112	1.50	<0.005		0.001
	406.00	407.50	D003113	1.50	<0.005		0.001
	407.50	409.00	D003114	1.50	<0.005		0.001
	409.00	410.50	D003115	1.50	<0.005		0.001
	410.50	412.00	D003116	1.50	<0.005		0.001
	412.00	413.50	D003118	1.50	<0.005		0.001
	413.50	415.00	D003119	1.50	<0.005		0.001
	415.00	416.50	D003121	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	416.50	418.00	D003122	1.50	0.186		0.186
	418.00	419.50	D003123	1.50	<0.005		0.001
	419.50	421.00	D003124	1.50	<0.005		0.001
	421.00	422.50	D003125	1.50	<0.005		0.001
	422.50	424.00	D003126	1.50	<0.005		0.001
	424.00	425.50	D003127	1.50	<0.005		0.001
	425.50	427.00	D003128	1.50	<0.005		0.001
	427.00	428.50	D003129	1.50	<0.005		0.001
	428.50	430.00	D003131	1.50	0.035		0.035
	430.00	431.50	D003132	1.50	<0.005		0.001
	431.50	433.00	D003133	1.50	<0.005		0.001
	433.00	434.50	D003134	1.50	<0.005		0.001
	434.50	436.00	D003135	1.50	0.028		0.028
	436.00	437.50	D003136	1.50	0.014		0.014
	437.50	439.00	D003137	1.50	0.042		0.042
	439.00	440.50	D003138	1.50	0.083		0.083
	440.50	442.00	D003139	1.50	0.010		0.010
	442.00	443.50	D003141	1.50	<0.005		0.001
	443.50	445.00	D003142	1.50	0.006		0.006
	445.00	446.50	D003143	1.50	0.005		0.005
	446.50	448.00	D003144	1.50	<0.005		0.001
	448.00	449.50	D003145	1.50	0.012		0.012
	449.50	451.00	D003146	1.50	<0.005		0.001
	451.00	452.50	D003147	1.50	0.018		0.018
	452.50	454.00	D003148	1.50	0.009		0.009
	454.00	455.50	D003149	1.50	0.008		0.008
	455.50	457.00	D003151	1.50	0.008		0.008
	457.00	458.50	D003152	1.50	0.006		0.006
	458.50	460.00	D003153	1.50	0.026		0.026
459.40	462.80	FRC	460.00	461.50	D003154	1.50	0.005
		<b>Fracturé 30°</b>	461.50	463.00	D003155	1.50	<0.005
		fragments 2-10cm	463.00	464.50	D003156	1.50	0.005
			464.50	466.00	D003158	1.50	0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
466.80	467.00	FRC Fracturé fragments 2-5 cm	466.00	467.50	D003159	1.50	0.090		0.090	
			467.50	469.00	D003161	1.50	<0.005		0.001	
			469.00	470.50	D003162	1.50	<0.005		0.001	
			470.50	472.00	D003163	1.50	<0.005		0.001	
			472.00	473.00	D003164	1.00	0.006		0.006	
473.00	Fin du sondage Nombre d'échantillons : 319 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 472.10									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.50	14.00	D002810	D002809	1.50	0.005	0.005
25.00	25.00	D002820	A3	0.00	0.593	0.593
38.50	40.00	D002830	D002829	1.50	<0.005	0.001
46.50	46.50	D002837	M1	0.00	<0.005	0.001
49.50	49.50	D002840	B4	0.00	2.650	2.650
63.00	64.50	D002850	D002849	1.50	0.018	0.018
76.00	76.00	D002860	C4	0.00	1.335	1.335
89.50	91.00	D002870	D002869	1.50	0.009	0.009
98.50	98.50	D002877	M1	0.00	<0.005	0.001
101.50	101.50	D002880	D2	0.00	0.813	0.813
115.00	116.50	D002890	D002889	1.50	0.432	0.432
128.00	128.00	D002900	F2	0.00	8.700	8.700
141.50	142.50	D002910	D002909	1.00	1.360	1.360
149.70	149.70	D002917	M1	0.00	0.005	0.005
152.50	152.50	D002920	G2	0.00	4.140	4.140
165.50	167.00	D002930	D002929	1.50	0.015	0.015
179.00	179.00	D002940	H	0.00	0.969	0.969
192.50	194.00	D002950	D002949	1.50	<0.005	0.001
201.50	201.50	D002957	M1	0.00	<0.005	0.001
206.00	206.00	D002960	A3	0.00	0.594	0.594
218.00	219.50	D002970	D002969	1.50	<0.005	0.001
231.50	231.50	D002980	B4	0.00	2.690	2.690
245.00	246.50	D002990	D002989	1.50	<0.005	0.001
254.00	254.00	D002997	M1	0.00	<0.005	0.001
257.00	257.00	D003000	C4	0.00	1.265	1.265
270.00	271.50	D003010	D003009	1.50	0.804	0.804
283.00	283.00	D003020	D2	0.00	0.858	0.858
296.50	298.00	D003030	D003029	1.50	0.236	0.236
305.50	305.50	D003037	M1	0.00	<0.005	0.001
308.50	308.50	D003040	G2	0.00	4.050	4.050
322.00	323.50	D003050	D003049	1.50	0.052	0.052
335.50	335.50	D003060	F2	0.00	8.250	8.250
349.00	350.50	D003070	D003069	1.50	0.009	0.009

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
358.00	358.00	D003077	M1	0.00	<0.005	0.001
361.00	361.00	D003080	H	0.00	0.997	0.997
374.50	376.00	D003090	D003089	1.50	0.065	0.065
388.00	388.00	D003100	A3	0.00	0.604	0.604
401.50	403.00	D003110	D003109	1.50	<0.005	0.001
410.50	410.50	D003117	M1	0.00	<0.005	0.001
413.50	413.50	D003120	B4	0.00	2.620	2.620
427.00	428.50	D003130	D003129	1.50	0.007	0.007
440.50	440.50	D003140	C4	0.00	1.375	1.375
454.00	455.50	D003150	D003149	1.50	0.010	0.010
463.00	463.00	D003157	M1	0.00	<0.005	0.001
466.00	466.00	D003160	D2	0.00	0.865	0.865



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-158**

Titre minier :

Section :                      631200

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Ciara Cooke / Guy Gbaguidi

Lot :

Du :                              2010-04-06

Date de description :

Au :                              2010-04-10

Collet

UTM

Azimut :                      0.00°

Plongée :                      -60.00°

Longueur :                      467.00 m

Est                              631 200.2

Nord                              5 374 250.0

Élévation                      310.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	0.00°	0.00°	Oui
Reflex	8.00	359.90°	-61.60°	Non
Reflex	11.00	358.90°	-60.20°	Non
Reflex	14.00	359.00°	-60.40°	Non
Reflex	17.00	359.00°	-60.40°	Non
Reflex	20.00	358.80°	-60.20°	Non
Reflex	23.00	357.10°	-56.80°	Non
Reflex	26.00	359.00°	-60.40°	Non
Reflex	29.00	359.20°	-60.30°	Non
Reflex	32.00	359.10°	-60.30°	Non
Reflex	35.00	359.30°	-60.40°	Non
Reflex	38.00	359.80°	-60.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	41.00	359.60°	-60.50°	Non
Reflex	44.00	359.50°	-60.50°	Non
Reflex	47.00	359.50°	-60.50°	Non
Reflex	50.00	359.70°	-60.50°	Non
Reflex	53.00	359.80°	-60.70°	Non
Reflex	56.00	359.80°	-60.60°	Non
Reflex	59.00	0.20°	-60.60°	Non
Reflex	62.00	0.10°	-60.70°	Non
Reflex	65.00	0.20°	-60.60°	Non
Reflex	68.00	0.10°	-60.60°	Non
Reflex	71.00	0.10°	-60.50°	Non
Reflex	74.00	0.10°	-60.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	77.00	0.20°	-60.40°	Non
Reflex	80.00	0.10°	-60.40°	Non
Reflex	83.00	0.00°	-60.20°	Non
Reflex	86.00	360.00°	-60.20°	Non
Reflex	89.00	359.90°	-60.10°	Non
Reflex	92.00	360.00°	-60.10°	Non
Reflex	95.00	360.00°	-60.00°	Non
Reflex	98.00	0.10°	-60.00°	Non
Reflex	101.00	360.00°	-59.90°	Non
Reflex	104.00	0.10°	-59.90°	Non
Reflex	107.00	0.20°	-59.80°	Non
Reflex	110.00	0.00°	-59.70°	Non
Reflex	113.00	0.10°	-59.70°	Non
Reflex	116.00	360.00°	-59.70°	Non
Reflex	119.00	0.10°	-59.70°	Non
Reflex	122.00	0.10°	-59.60°	Non
Reflex	125.00	0.10°	-59.50°	Non
Reflex	128.00	0.10°	-59.50°	Non
Reflex	131.00	0.10°	-59.50°	Non
Reflex	134.00	0.30°	-59.40°	Non
Reflex	137.00	0.20°	-59.30°	Non
Reflex	140.00	0.40°	-59.30°	Non
Reflex	143.00	0.60°	-59.20°	Non
Reflex	146.00	0.70°	-59.10°	Non
Reflex	149.00	0.50°	-59.00°	Non
Reflex	152.00	0.40°	-58.90°	Non
Reflex	155.00	1.50°	-58.90°	Non
Reflex	158.00	1.20°	-58.80°	Non
Reflex	161.00	1.40°	-58.80°	Non
Reflex	164.00	1.10°	-58.80°	Non
Reflex	167.00	1.10°	-58.70°	Non
Reflex	170.00	1.10°	-58.60°	Non
Reflex	173.00	0.80°	-58.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	176.00	0.80°	-58.40°	Non
Reflex	179.00	0.80°	-58.40°	Non
Reflex	182.00	1.00°	-58.50°	Non
Reflex	185.00	0.50°	-58.30°	Non
Reflex	188.00	1.10°	-58.50°	Non
Reflex	191.00	1.20°	-58.50°	Non
Reflex	194.00	1.50°	-58.50°	Non
Reflex	197.00	3.00°	-58.50°	Oui
Reflex	200.00	2.00°	-58.50°	Non
Reflex	203.00	1.40°	-58.50°	Non
Reflex	206.00	1.50°	-58.50°	Non
Reflex	209.00	1.50°	-58.50°	Non
Reflex	212.00	1.50°	-58.50°	Non
Reflex	215.00	1.50°	-58.50°	Non
Reflex	218.00	0.90°	-58.50°	Non
Reflex	221.00	0.20°	-58.50°	Non
Reflex	224.00	3.80°	-58.40°	Oui
Reflex	227.00	2.90°	-58.50°	Non
Reflex	230.00	1.60°	-58.40°	Non
Reflex	233.00	2.00°	-58.40°	Non
Reflex	236.00	2.00°	-58.50°	Non
Reflex	239.00	2.40°	-58.40°	Non
Reflex	242.00	2.50°	-58.30°	Non
Reflex	245.00	2.70°	-58.40°	Non
Reflex	248.00	2.60°	-58.30°	Non
Reflex	251.00	2.50°	-58.20°	Non
Reflex	254.00	2.60°	-58.40°	Non
Reflex	257.00	1.50°	-58.40°	Non
Reflex	260.00	1.50°	-58.40°	Non
Reflex	263.00	3.20°	-58.40°	Non
Reflex	266.00	3.30°	-58.30°	Non
Reflex	269.00	3.10°	-58.30°	Non
Reflex	272.00	3.00°	-58.30°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	275.00	2.70°	-58.30°	Non	Reflex	374.00	5.80°	-57.90°	Non
Reflex	278.00	2.80°	-58.40°	Non	Reflex	377.00	4.50°	-57.90°	Non
Reflex	281.00	1.60°	-58.30°	Oui	Reflex	380.00	3.70°	-57.80°	Non
Reflex	284.00	3.40°	-58.30°	Non	Reflex	383.00	3.90°	-57.90°	Non
Reflex	287.00	2.20°	-58.30°	Non	Reflex	386.00	5.90°	-57.80°	Non
Reflex	290.00	1.70°	-58.30°	Oui	Reflex	389.00	4.50°	-57.80°	Non
Reflex	293.00	2.30°	-58.30°	Non	Reflex	392.00	5.20°	-57.90°	Non
Reflex	296.00	4.20°	-58.30°	Non	Reflex	395.00	5.00°	-57.90°	Non
Reflex	299.00	5.80°	-58.30°	Non	Reflex	398.00	4.50°	-57.90°	Non
Reflex	302.00	3.90°	-58.30°	Non	Reflex	401.00	5.80°	-57.80°	Non
Reflex	305.00	4.00°	-58.30°	Non	Reflex	404.00	5.50°	-57.90°	Non
Reflex	308.00	3.70°	-58.40°	Non	Reflex	407.00	5.20°	-57.80°	Non
Reflex	311.00	3.70°	-58.40°	Non	Reflex	410.00	3.80°	-57.80°	Non
Reflex	314.00	3.80°	-58.30°	Non	Reflex	413.00	4.70°	-57.70°	Non
Reflex	317.00	4.00°	-58.30°	Non	Reflex	416.00	4.20°	-57.80°	Non
Reflex	320.00	3.60°	-58.00°	Non	Reflex	419.00	6.40°	-57.80°	Non
Reflex	323.00	3.90°	-58.20°	Non	Reflex	422.00	6.20°	-57.80°	Non
Reflex	326.00	4.30°	-58.20°	Non	Reflex	425.00	6.70°	-57.80°	Non
Reflex	329.00	4.50°	-58.20°	Non	Reflex	428.00	6.20°	-57.70°	Non
Reflex	332.00	4.90°	-58.20°	Non	Reflex	431.00	5.70°	-57.70°	Non
Reflex	335.00	5.20°	-58.20°	Non	Reflex	434.00	6.50°	-57.80°	Non
Reflex	338.00	5.40°	-58.10°	Non	Reflex	437.00	7.20°	-57.80°	Non
Reflex	341.00	5.80°	-58.20°	Non	Reflex	440.00	8.10°	-57.80°	Non
Reflex	344.00	5.30°	-58.10°	Non	Reflex	443.00	6.60°	-57.80°	Non
Reflex	347.00	5.10°	-58.10°	Non	Reflex	446.00	7.80°	-57.80°	Non
Reflex	350.00	5.10°	-58.00°	Non	Reflex	449.00	7.60°	-57.70°	Non
Reflex	353.00	3.70°	-58.00°	Non	Reflex	452.00	7.80°	-57.70°	Non
Reflex	356.00	3.80°	-58.00°	Non	Reflex	455.00	3.60°	-57.70°	Oui
Reflex	359.00	3.00°	-57.90°	Non	Reflex	458.00	8.50°	-57.70°	Non
Reflex	362.00	3.40°	-57.90°	Non	Reflex	461.00	3.50°	-57.70°	Non
Reflex	365.00	4.40°	-57.90°	Non	Reflex	464.00	4.60°	-57.70°	Non
Reflex	368.00	7.30°	-57.80°	Non	Reflex	467.00	3.90°	-57.70°	Non
Reflex	371.00	4.30°	-58.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.00	MT <b>Mort-terrain</b> MT							
2.00	8.60	SY; POR <b>Syénite; Porphyrique</b> Porphyritic syenite. Hematite alteration. Localized areas of oxidation. Localized areas of sericite and chlorite alteration. Gradual contact with below unit.	2.00	3.50	D013141	1.50	0.049		0.049
			3.50	5.00	D013142	1.50	0.006		0.006
			5.00	6.00	D013143	1.00	0.011		0.011
			6.00	7.00	D013144	1.00	0.006		0.006
			7.00	8.60	D013146	1.60	0.005		0.005
8.60	10.20	PT <b>Porphyre trachytique</b> Porphyritic trachyte. Sericite and chlorite alteration. Localized areas of oxidation. No alignment to plagioclase phenocrysts.	8.60	10.20	D013147	1.60	0.029		0.029
10.20	155.10	BA; AMY; BR <b>Basalte 45°; Amygdalaire; Bréchifié</b> Amygdalaire Basalt with moderate shearing. Amygdules of quartz-carbonates (up to 3cm). Sericite alteration. Regions of high chlorite and hematite alteration in upper units (above 66.1m). Replacement, silicification and localized brecciation.	10.20	11.90	D013148	1.70	0.541		0.541
			11.90	13.50	D013149	1.60	0.154		0.154
			13.50	15.00	D013150	1.50	0.019		0.019
			15.00	16.50	D013151	1.50	0.034		0.034
			16.50	18.00	D013152	1.50	0.070		0.070
			18.00	19.50	D013153	1.50	0.128		0.128
			19.50	21.00	D013154	1.50	0.033		0.033
			21.00	22.50	D013156	1.50	0.020		0.020
			22.50	24.00	D013157	1.50	0.145		0.145
			24.00	25.50	D013158	1.50	0.141		0.141
			25.50	27.00	D013159	1.50	0.280		0.280
			27.00	28.50	D013161	1.50	0.076		0.076
			28.50	30.00	D013162	1.50	0.327		0.327
			30.00	31.60	D013163	1.60	0.689		0.689
			31.60	33.70	D013164	2.10	0.088		0.088
			33.70	35.00	D013166	1.30	0.014		0.014
			35.00	36.50	D013167	1.50	0.034		0.034
			36.50	38.00	D013168	1.50	0.039		0.039
			38.00	39.50	D013169	1.50	0.014		0.014
			39.50	41.00	D013170	1.50	0.016		0.016
			41.00	42.50	D013171	1.50	0.018		0.018
			42.50	44.00	D013172	1.50	0.811		0.811

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	44.00	45.50	D013173	1.50	0.085		0.085
	45.50	47.00	D013174	1.50	0.093		0.093
	47.00	48.50	D013176	1.50	0.110		0.110
	48.50	50.00	D013177	1.50	0.075		0.075
	50.00	51.50	D013178	1.50	0.616		0.616
	51.50	53.00	D013179	1.50	0.086		0.086
	53.00	54.50	D013180	1.50	0.162		0.162
	54.50	56.00	D013181	1.50	0.154		0.154
	56.00	57.50	D013182	1.50	0.103		0.103
	57.50	59.00	D013183	1.50	0.638		0.638
	59.00	60.50	D013184	1.50	0.311		0.311
	60.50	62.00	D013186	1.50	0.418		0.418
	62.00	63.50	D013187	1.50	0.061		0.061
	63.50	65.00	D013188	1.50	0.126		0.126
	65.00	66.10	D013189	1.10	0.437		0.437
	66.10	67.80	D013190	1.70	2.350		2.350
	67.80	69.50	D013191	1.70	0.009		0.009
	69.50	71.00	D013192	1.50	0.007		0.007
	71.00	72.50	D013193	1.50	0.006		0.006
	72.50	74.00	D013194	1.50	0.018		0.018
	74.00	75.50	D013196	1.50	0.010		0.010
	75.50	77.00	D013197	1.50	0.008		0.008
	77.00	78.50	D013198	1.50	0.006		0.006
	78.50	80.00	D013199	1.50	0.008		0.008
	80.00	81.50	D013200	1.50	0.008		0.008
	81.50	83.00	D013201	1.50	0.025		0.025
	83.00	84.50	D013202	1.50	0.049		0.049
	84.50	86.00	D013203	1.50	0.006		0.006
	86.00	87.50	D013204	1.50	0.007		0.007
	87.50	89.00	D013206	1.50	0.005		0.005
	89.00	90.50	D013207	1.50	0.005		0.005
	90.50	92.00	D013208	1.50	0.006		0.006
	92.00	93.50	D013209	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	93.50	95.00	D013210	1.50	0.006		0.006
	95.00	96.50	D013211	1.50	0.005		0.005
	96.50	98.00	D013212	1.50	0.007		0.007
	98.00	99.50	D013213	1.50	<0.005		0.001
	99.50	101.00	D013214	1.50	0.005		0.005
	101.00	102.50	D013216	1.50	<0.005		0.001
	102.50	104.00	D013217	1.50	0.005		0.005
	104.00	105.50	D013218	1.50	0.008		0.008
	105.50	107.00	D013219	1.50	0.006		0.006
	107.00	108.50	D013220	1.50	<0.005		0.001
	108.50	110.00	D013221	1.50	0.006		0.006
	110.00	111.50	D013222	1.50	<0.005		0.001
	111.50	113.00	D013223	1.50	<0.005		0.001
	113.00	114.50	D013224	1.50	0.005		0.005
	114.50	116.00	D013226	1.50	<0.005		0.001
	116.00	117.50	D013227	1.50	0.008		0.008
	117.50	119.00	D013228	1.50	0.006		0.006
	119.00	120.50	D013229	1.50	<0.005		0.001
	120.50	122.00	D013230	1.50	<0.005		0.001
	122.00	123.50	D013231	1.50	<0.005		0.001
	123.50	125.00	D013232	1.50	<0.005		0.001
	125.00	126.50	D013233	1.50	<0.005		0.001
	126.50	128.00	D013234	1.50	<0.005		0.001
	128.00	129.50	D013236	1.50	0.006		0.006
	129.50	131.00	D013237	1.50	0.009		0.009
	131.00	132.50	D013238	1.50	0.009		0.009
	132.50	134.00	D013239	1.50	<0.005		0.001
	134.00	135.50	D013241	1.50	0.024		0.024
	135.50	137.00	D013242	1.50	0.017		0.017
	137.00	138.50	D013243	1.50	0.009		0.009
	138.50	140.00	D013244	1.50	0.037		0.037
	140.00	141.50	D013246	1.50	0.005		0.005
	141.50	143.00	D013247	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			143.00	144.50	D013248	1.50	<0.005		0.001
			144.50	146.00	D013249	1.50	0.006		0.006
			146.00	147.50	D013250	1.50	<0.005		0.001
			147.50	149.00	D013251	1.50	<0.005		0.001
			149.00	150.50	D013252	1.50	<0.005		0.001
			150.50	152.00	D013253	1.50	<0.005		0.001
			152.00	153.50	D013254	1.50	<0.005		0.001
			153.50	155.10	D013256	1.60	0.005		0.005
155.10	159.40	TU <b>Tuf à cendre/lapillis 45°</b> Lapilli-block-bomb tuff. Bombs up to 5cm. Sheared to 75-degrees. Sericitic and chlorite alteration.	155.10	156.00	D013257	0.90	<0.005		0.001
			156.00	157.70	D013258	1.70	<0.005		0.001
			157.70	159.40	D013259	1.70	<0.005		0.001
159.40	167.00	SY; POR <b>Syénite 45°; Porphyrique</b> Porphyritic syenite. Hemtite and sericite alteration. Locally chloritized. Locally brecciated.	159.40	161.00	D013260	1.60	<0.005		0.001
			161.00	162.50	D013261	1.50	<0.005		0.001
			162.50	164.00	D013262	1.50	<0.005		0.001
			164.00	165.50	D013263	1.50	0.834		0.834
			165.50	167.00	D013264	1.50	<0.005		0.001
167.00	173.70	BA; AMY <b>Basalte 60°; Amygdalaire</b> Amygdalaire basalt. Sericite and chlorite alteration. Local hematite alteration. Sheared.	167.00	168.50	D013266	1.50	<0.005		0.001
			168.50	170.00	D013267	1.50	<0.005		0.001
			170.00	171.50	D013268	1.50	0.023		0.023
			171.50	172.50	D013269	1.00	<0.005		0.001
			172.50	173.50	D013270	1.00	0.279		0.279
			173.50	175.00	D013271	1.50	<0.005		0.001
173.70	467.00	SY; POR <b>Syénite 60°; Porphyrique</b> Porphyritic syenite. Hematite alteration. Locally silicified (beginning at 241.5m) and brecciated. Local chlorite and sericite alteration. Locally magnetic in areas of strong hematite alteration (beginning around 250m).	175.00	176.50	D013272	1.50	<0.005		0.001
			176.50	178.00	D013273	1.50	0.005		0.005
			178.00	179.50	D013274	1.50	0.007		0.007
			179.50	181.00	D013276	1.50	0.040		0.040
			181.00	182.50	D013277	1.50	0.005		0.005
			182.50	184.00	D013278	1.50	<0.005		0.001
			184.00	185.50	D013279	1.50	0.093		0.093
			185.50	187.00	D013281	1.50	0.171		0.171
			187.00	188.50	D013282	1.50	<0.005		0.001
			188.50	190.00	D013283	1.50	0.020		0.020
	190.00	191.50	D013284	1.50	0.024		0.024		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	191.50	193.00	D013286	1.50	0.016		0.016
	193.00	194.50	D013287	1.50	0.021		0.021
	194.50	196.00	D013288	1.50	0.011		0.011
	196.00	197.50	D013289	1.50	0.005		0.005
	197.50	199.00	D013290	1.50	0.009		0.009
	199.00	200.50	D013291	1.50	0.486		0.486
	200.50	202.00	D013292	1.50	0.057		0.057
	202.00	203.50	D013293	1.50	0.282		0.282
	203.50	205.00	D013294	1.50	0.038		0.038
	205.00	206.50	D013296	1.50	0.008		0.008
	206.50	208.00	D013297	1.50	0.008		0.008
	208.00	209.50	D013298	1.50	<0.005		0.001
	209.50	211.00	D013299	1.50	0.010		0.010
	211.00	212.50	D013300	1.50	0.018		0.018
	212.50	214.00	D013301	1.50	0.024		0.024
	214.00	215.50	D013302	1.50	0.084		0.084
	215.50	217.00	D013303	1.50	0.102		0.102
	217.00	218.50	D013304	1.50	0.015		0.015
	218.50	220.00	D013306	1.50	1.125		1.125
	220.00	221.50	D013307	1.50	0.008		0.008
	221.50	223.00	D013308	1.50	0.086		0.086
	223.00	224.50	D013309	1.50	0.032		0.032
	224.50	226.00	D013310	1.50	0.060		0.060
	226.00	227.00	D013311	1.00	0.047		0.047
	227.00	228.50	D013312	1.50	0.090		0.090
	228.50	230.00	D013313	1.50	0.480		0.480
	230.00	231.50	D013314	1.50	0.163		0.163
	231.50	233.00	D013316	1.50	0.445		0.445
	233.00	234.50	D013317	1.50	0.083		0.083
	234.50	236.00	D013318	1.50	0.152		0.152
	236.00	237.50	D013319	1.50	0.151		0.151
	237.50	239.00	D013321	1.50	0.180		0.180
	239.00	240.50	D013322	1.50	0.123		0.123



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	240.50	242.00	D013323	1.50	1.595		1.595
	242.00	243.50	D013324	1.50	1.770		1.770
	243.50	245.00	D013326	1.50	1.800		1.800
	245.00	246.00	D013327	1.00	2.970		2.970
	246.00	247.00	D013328	1.00	2.440		2.440
	247.00	248.40	D013329	1.40	4.670		4.670
	248.40	250.00	D013330	1.60	0.038		0.038
	250.00	251.50	D013331	1.50	0.015		0.015
	251.50	253.00	D013332	1.50	0.042		0.042
	253.00	254.50	D013333	1.50	0.046		0.046
	254.50	256.00	D013334	1.50	0.318		0.318
	256.00	257.50	D013336	1.50	0.010		0.010
	257.50	259.00	D013337	1.50	0.010		0.010
	259.00	260.50	D013338	1.50	0.031		0.031
	260.50	262.00	D013339	1.50	<0.005		0.001
	262.00	263.50	D013340	1.50	0.019		0.019
	263.50	265.00	D013341	1.50	0.017		0.017
	265.00	266.50	D013342	1.50	0.069		0.069
	266.50	268.00	D013343	1.50	0.751		0.751
	268.00	269.50	D013344	1.50	0.006		0.006
	269.50	271.00	D013346	1.50	0.013		0.013
	271.00	272.50	D013347	1.50	0.006		0.006
	272.50	274.00	D013348	1.50	0.012		0.012
	274.00	275.00	D013349	1.00	0.167		0.167
	275.00	276.00	D013350	1.00	0.084		0.084
	276.00	277.50	D013351	1.50	0.010		0.010
	277.50	279.00	D013352	1.50	0.123		0.123
	279.00	280.50	D013353	1.50	0.109		0.109
	280.50	282.00	D013354	1.50	0.018		0.018
	282.00	283.50	D013356	1.50	0.025		0.025
	283.50	285.00	D013357	1.50	0.027		0.027
	285.00	286.40	D013358	1.40	0.431		0.431
	286.40	288.00	D013359	1.60	0.037		0.037

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	288.00	289.50	D013361	1.50	0.243		0.243
	289.50	291.00	D013362	1.50	0.014		0.014
	291.00	292.50	D013363	1.50	0.012		0.012
	292.50	294.00	D013364	1.50	<0.005		0.001
	294.00	295.00	D013366	1.00	<0.005		0.001
	295.00	296.20	D013367	1.20	0.006		0.006
	296.20	297.70	D013368	1.50	0.071		0.071
	297.70	299.20	D013369	1.50	0.356		0.356
	299.20	300.00	D013370	0.80	0.528		0.528
	300.00	301.50	D013371	1.50	0.364		0.364
	301.50	303.00	D013372	1.50	0.187		0.187
	303.00	304.20	D013373	1.20	0.005		0.005
	304.20	305.20	D013374	1.00	<0.005		0.001
	305.20	306.50	D013376	1.30	0.006		0.006
	306.50	308.00	D013377	1.50	0.361		0.361
	308.00	309.00	D013378	1.00	0.822		0.822
	309.00	310.00	D013379	1.00	0.252		0.252
	310.00	311.50	D013380	1.50	0.502		0.502
	311.50	313.00	D013381	1.50	0.297		0.297
	313.00	314.50	D013382	1.50	0.011		0.011
	314.50	316.00	D013383	1.50	0.015		0.015
	316.00	317.00	D013384	1.00	0.064		0.064
	317.00	318.50	D013386	1.50	0.202		0.202
	318.50	320.00	D013387	1.50	1.375		1.375
	320.00	321.50	D013388	1.50	0.795		0.795
	321.50	323.00	D013389	1.50	0.028		0.028
	323.00	324.50	D013390	1.50	0.005		0.005
	324.50	326.00	D013391	1.50	<0.005		0.001
	326.00	327.50	D013392	1.50	<0.005		0.001
	327.50	329.00	D013393	1.50	<0.005		0.001
	329.00	330.00	D013394	1.00	<0.005		0.001
	330.00	331.30	D013396	1.30	0.005		0.005
	331.30	332.30	D013397	1.00	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	332.30	334.00	D013398	1.70	0.009		0.009
	334.00	335.70	D013399	1.70	0.030		0.030
	335.70	337.40	D013401	1.70	0.164		0.164
	337.40	339.00	D013402	1.60	0.008		0.008
	339.00	340.50	D013403	1.50	0.013		0.013
	340.50	342.00	D013404	1.50	<0.005		0.001
	342.00	343.50	D013406	1.50	<0.005		0.001
	343.50	345.00	D013407	1.50	0.005		0.005
	345.00	346.70	D013408	1.70	0.005		0.005
	346.70	348.20	D013409	1.50	0.096		0.096
	348.20	349.00	D013410	0.80	0.005		0.005
	349.00	350.20	D013411	1.20	0.009		0.009
	350.20	351.00	D013412	0.80	0.006		0.006
	351.00	352.00	D013413	1.00	0.844		0.844
	352.00	353.40	D013414	1.40	0.043		0.043
	353.40	354.40	D013416	1.00	0.602		0.602
	354.40	356.00	D013417	1.60	1.100		1.100
	356.00	357.00	D013418	1.00	0.006		0.006
	357.00	358.50	D013419	1.50	0.010		0.010
	358.50	360.00	D013420	1.50	1.110		1.110
	360.00	361.50	D013421	1.50	0.155		0.155
	361.50	363.00	D013422	1.50	1.505		1.505
	363.00	364.50	D013423	1.50	0.182		0.182
	364.50	366.00	D013424	1.50	0.285		0.285
	366.00	367.50	D013426	1.50	0.005		0.005
	367.50	369.00	D013427	1.50	0.009		0.009
	369.00	370.50	D013428	1.50	0.094		0.094
	370.50	372.00	D013429	1.50	0.125		0.125
	372.00	373.50	D013430	1.50	0.459		0.459
	373.50	375.00	D013431	1.50	0.018		0.018
	375.00	376.50	D013432	1.50	0.017		0.017
	376.50	378.00	D013433	1.50	0.406		0.406
	378.00	379.50	D013434	1.50	0.095		0.095

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	379.50	381.00	D013436	1.50	0.018		0.018
	381.00	382.50	D013437	1.50	0.011		0.011
	382.50	384.00	D013438	1.50	0.009		0.009
	384.00	385.50	D013439	1.50	0.009		0.009
	385.50	387.00	D013441	1.50	0.005		0.005
	387.00	388.50	D013442	1.50	0.051		0.051
	388.50	390.00	D013443	1.50	0.060		0.060
	390.00	391.50	D013444	1.50	0.011		0.011
	391.50	393.00	D013446	1.50	<0.005		0.001
	393.00	394.50	D013447	1.50	0.033		0.033
	394.50	396.00	D013448	1.50	0.552		0.552
	396.00	397.50	D013449	1.50	0.031		0.031
	397.50	399.00	D013450	1.50	0.011		0.011
	399.00	400.50	D013451	1.50	0.005		0.005
	400.50	402.00	D013452	1.50	0.005		0.005
	402.00	403.50	D013453	1.50	0.153		0.153
	403.50	405.00	D013454	1.50	1.995		1.995
	405.00	406.50	D013456	1.50	0.146		0.146
	406.50	408.00	D013457	1.50	<0.005		0.001
	408.00	409.50	D013458	1.50	0.005		0.005
	409.50	411.00	D013459	1.50	<0.005		0.001
	411.00	412.50	D013460	1.50	<0.005		0.001
	412.50	414.00	D013461	1.50	<0.005		0.001
	414.00	415.50	D013462	1.50	0.006		0.006
	415.50	417.00	D013463	1.50	0.750		0.750
	417.00	418.50	D013464	1.50	0.051		0.051
	418.50	420.00	D013466	1.50	0.017		0.017
	420.00	421.50	D013467	1.50	0.440		0.440
	421.50	423.00	D013468	1.50	0.012		0.012
	423.00	424.50	D013469	1.50	2.110		2.110
	424.50	426.00	D013470	1.50	0.325		0.325
	426.00	427.50	D013471	1.50	0.018		0.018
	427.50	429.00	D013472	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	429.00	430.50	D013473	1.50	<0.005		0.001
	430.50	432.00	D013474	1.50	0.009		0.009
	432.00	433.50	D013476	1.50	0.006		0.006
	433.50	435.00	D013477	1.50	0.142		0.142
	435.00	436.50	D013478	1.50	0.010		0.010
	436.50	438.00	D013479	1.50	0.007		0.007
	438.00	439.50	D013481	1.50	0.020		0.020
	439.50	441.00	D013482	1.50	0.007		0.007
	441.00	442.50	D013483	1.50	0.008		0.008
	442.50	444.00	D013484	1.50	0.007		0.007
	444.00	445.50	D013486	1.50	0.021		0.021
	445.50	447.00	D013487	1.50	0.010		0.010
	447.00	448.00	D013488	1.00	0.034		0.034
	448.00	449.00	D013489	1.00	1.185		1.185
	449.00	450.50	D013490	1.50	2.130		2.130
	450.50	452.00	D013491	1.50	0.297		0.297
	452.00	453.40	D013492	1.40	<0.005		0.001
	453.40	455.00	D013493	1.60	0.468		0.468
	455.00	456.50	D013494	1.50	0.795		0.795
	456.50	458.00	D013496	1.50	0.394		0.394
	458.00	459.50	D013497	1.50	0.600		0.600
	459.50	460.50	D013498	1.00	0.164		0.164
	460.50	462.00	D013499	1.50	0.010		0.010
	462.00	463.50	D013500	1.50	0.051		0.051
	463.50	465.00	D013501	1.50	0.144		0.144
	465.00	466.00	D013502	1.00	0.085		0.085
	466.00	467.00	D013503	1.00	0.012		0.012
467.00	Fin du sondage Nombre d'échantillons : 319 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 465.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	7.00	D013145	D013144	1.00	0.005	0.005
19.50	19.50	D013155	D2	0.00	0.864	0.864
24.00	24.00	D013160	M1	0.00	0.005	0.005
31.60	33.70	D013165	D013164	2.10	0.071	0.071
45.50	45.50	D013175	F2	0.00	8.340	8.340
59.00	60.50	D013185	D013184	1.50	0.377	0.377
72.50	72.50	D013195	H	0.00	0.976	0.976
86.00	87.50	D013205	D013204	1.50	<0.005	0.001
99.50	99.50	D013215	A3	0.00	0.615	0.615
113.00	114.50	D013225	D013224	1.50	<0.005	0.001
126.50	126.50	D013235	B4	0.00	2.570	2.570
132.50	132.50	D013240	M1	0.00	<0.005	0.001
138.50	140.00	D013245	D013244	1.50	0.085	0.085
152.00	152.00	D013255	C4	0.00	1.275	1.275
165.50	167.00	D013265	D013264	1.50	<0.005	0.001
178.00	178.00	D013275	D2	0.00	0.854	0.854
184.00	184.00	D013280	M1	0.00	<0.005	0.001
190.00	191.50	D013285	D013284	1.50	0.017	0.017
203.50	203.50	D013295	G2	0.00	4.020	4.020
217.00	218.50	D013305	D013304	1.50	0.028	0.028
230.00	230.00	D013315	H	0.00	0.969	0.969
236.00	236.00	D013320	M1	0.00	<0.005	0.001
242.00	243.50	D013325	D013324	1.50	1.735	1.735
254.50	254.50	D013335	A3	0.00	0.604	0.604
268.00	269.50	D013345	D013344	1.50	0.006	0.006
280.50	280.50	D013355	B4	0.00	2.550	2.550
286.40	286.40	D013360	M1	0.00	<0.005	0.001
292.50	294.00	D013365	D013364	1.50	0.005	0.005
304.20	304.20	D013375	C4	0.00	1.350	1.350
316.00	317.00	D013385	D013384	1.00	0.068	0.068
329.00	329.00	D013395	D2	0.00	0.814	0.814
334.00	334.00	D013400	M1	0.00	<0.005	0.001
340.50	342.00	D013405	D013404	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
352.00	352.00	D013415	F2	0.00	8.320	8.320
364.50	366.00	D013425	D013424	1.50	0.162	0.162
378.00	378.00	D013435	H	0.00	0.991	0.991
384.00	384.00	D013440	M1	0.00	<0.005	0.001
390.00	391.50	D013445	D013444	1.50	0.005	0.005
403.50	403.50	D013455	A3	0.00	0.496	0.496
417.00	418.50	D013465	D013464	1.50	0.026	0.026
430.50	430.50	D013475	B4	0.00	2.620	2.620
436.50	436.50	D013480	M1	0.00	<0.005	0.001
442.50	444.00	D013485	D013484	1.50	0.007	0.007
455.00	455.00	D013495	C4	0.00	1.335	1.335

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-159**

Titre minier :

Section :                      631200

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles.KAMTA

Lot :

Du :                              2010-04-10

Date de description :              2010-05-11

Au :                              2010-04-14

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      476.00 m

Est	631 200.0
Nord	5 374 300.3
Élévation	308.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	1.40°	-60.20°	Non
Reflex	8.00	0.50°	-59.90°	Non
Reflex	11.00	0.10°	-59.80°	Non
Reflex	14.00	359.90°	-59.80°	Non
Reflex	17.00	359.80°	-59.70°	Non
Reflex	20.00	359.80°	-59.60°	Non
Reflex	23.00	359.70°	-59.50°	Non
Reflex	26.00	359.80°	-59.50°	Non
Reflex	29.00	359.80°	-59.40°	Non
Reflex	32.00	359.80°	-59.40°	Non
Reflex	35.00	359.80°	-59.30°	Non
Reflex	38.00	359.80°	-59.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	41.00	359.80°	-59.20°	Non
Reflex	44.00	359.90°	-59.20°	Non
Reflex	47.00	0.20°	-59.10°	Non
Reflex	50.00	0.20°	-59.00°	Non
Reflex	53.00	0.10°	-58.90°	Non
Reflex	56.00	0.60°	-58.80°	Non
Reflex	59.00	1.00°	-58.80°	Non
Reflex	62.00	0.30°	-58.70°	Non
Reflex	65.00	0.40°	-58.70°	Non
Reflex	68.00	4.00°	-58.70°	Oui
Reflex	71.00	10.20°	-58.40°	Oui
Reflex	74.00	0.90°	-58.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	77.00	1.80°	-58.30°	Non	Reflex	176.00	2.90°	-56.90°	Non
Reflex	80.00	0.30°	-58.20°	Non	Reflex	179.00	3.00°	-56.70°	Non
Reflex	83.00	1.80°	-58.20°	Non	Reflex	182.00	3.10°	-56.60°	Non
Reflex	86.00	1.30°	-58.10°	Non	Reflex	185.00	3.20°	-56.40°	Non
Reflex	89.00	1.30°	-58.10°	Non	Reflex	188.00	3.30°	-56.30°	Non
Reflex	92.00	1.20°	-58.00°	Non	Reflex	191.00	3.50°	-56.30°	Non
Reflex	95.00	1.20°	-58.00°	Non	Reflex	194.00	3.80°	-56.30°	Non
Reflex	98.00	1.30°	-58.00°	Non	Reflex	197.00	3.70°	-56.20°	Non
Reflex	101.00	1.30°	-58.00°	Non	Reflex	200.00	3.90°	-56.10°	Non
Reflex	104.00	1.40°	-57.90°	Non	Reflex	203.00	4.00°	-56.00°	Non
Reflex	107.00	1.40°	-57.90°	Non	Reflex	206.00	4.40°	-56.10°	Non
Reflex	110.00	1.50°	-57.90°	Non	Reflex	209.00	4.60°	-56.10°	Non
Reflex	113.00	1.50°	-57.80°	Non	Reflex	212.00	4.70°	-55.90°	Non
Reflex	116.00	1.60°	-57.90°	Non	Reflex	215.00	4.90°	-55.90°	Non
Reflex	119.00	1.70°	-57.80°	Non	Reflex	218.00	5.10°	-55.90°	Non
Reflex	122.00	1.70°	-57.80°	Non	Reflex	221.00	5.00°	-55.90°	Non
Reflex	125.00	1.90°	-57.80°	Non	Reflex	224.00	4.80°	-55.90°	Non
Reflex	128.00	2.10°	-57.80°	Non	Reflex	227.00	4.70°	-55.90°	Non
Reflex	131.00	1.90°	-57.80°	Non	Reflex	230.00	4.30°	-55.80°	Non
Reflex	134.00	1.50°	-57.80°	Non	Reflex	233.00	4.20°	-55.80°	Non
Reflex	137.00	2.20°	-57.80°	Non	Reflex	236.00	3.90°	-55.90°	Non
Reflex	140.00	3.10°	-57.80°	Oui	Reflex	239.00	3.00°	-55.80°	Non
Reflex	143.00	1.50°	-57.80°	Non	Reflex	242.00	4.90°	-55.80°	Non
Reflex	146.00	2.50°	-57.70°	Non	Reflex	245.00	359.60°	-55.70°	Oui
Reflex	149.00	2.30°	-57.70°	Non	Reflex	248.00	5.50°	-55.80°	Non
Reflex	152.00	2.40°	-57.70°	Non	Reflex	251.00	4.50°	-55.80°	Non
Reflex	155.00	2.30°	-57.70°	Non	Reflex	254.00	5.90°	-55.80°	Non
Reflex	158.00	2.50°	-57.60°	Non	Reflex	257.00	4.60°	-55.70°	Non
Reflex	161.00	2.80°	-57.60°	Non	Reflex	260.00	5.60°	-55.70°	Non
Reflex	164.00	2.80°	-57.60°	Non	Reflex	263.00	6.00°	-55.60°	Non
Reflex	167.00	2.80°	-57.30°	Non	Reflex	266.00	5.30°	-55.60°	Non
Reflex	170.00	2.80°	-57.20°	Non	Reflex	269.00	6.00°	-55.70°	Non
Reflex	173.00	2.80°	-57.00°	Non	Reflex	272.00	5.10°	-55.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	275.00	4.20°	-55.70°	Non
Reflex	278.00	5.50°	-55.70°	Non
Reflex	281.00	5.40°	-55.70°	Non
Reflex	284.00	5.20°	-55.60°	Non
Reflex	287.00	5.00°	-55.70°	Non
Reflex	290.00	6.90°	-55.60°	Non
Reflex	293.00	6.30°	-55.60°	Non
Reflex	296.00	8.40°	-55.50°	Oui
Reflex	299.00	4.30°	-55.50°	Oui
Reflex	302.00	6.20°	-55.50°	Non
Reflex	305.00	8.40°	-55.50°	Oui
Reflex	308.00	6.20°	-55.50°	Non
Reflex	311.00	7.10°	-55.50°	Non
Reflex	314.00	6.70°	-55.60°	Non
Reflex	317.00	8.40°	-55.60°	Non
Reflex	320.00	7.50°	-55.60°	Non
Reflex	323.00	5.40°	-55.50°	Oui
Reflex	326.00	7.10°	-55.50°	Non
Reflex	329.00	6.10°	-55.50°	Non
Reflex	332.00	2.20°	-55.60°	Oui
Reflex	335.00	4.10°	-55.60°	Non
Reflex	338.00	4.10°	-55.60°	Non
Reflex	341.00	4.50°	-55.60°	Non
Reflex	344.00	2.60°	-55.50°	Oui
Reflex	347.00	5.20°	-55.50°	Non
Reflex	350.00	6.70°	-55.50°	Non
Reflex	353.00	8.10°	-55.50°	Non
Reflex	356.00	8.00°	-55.50°	Non
Reflex	359.00	9.20°	-55.50°	Non
Reflex	362.00	9.10°	-55.50°	Non
Reflex	365.00	9.40°	-55.50°	Non
Reflex	368.00	7.60°	-55.50°	Oui
Reflex	371.00	8.10°	-55.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	374.00	8.50°	-55.50°	Non
Reflex	377.00	8.10°	-55.50°	Non
Reflex	380.00	6.80°	-55.40°	Oui
Reflex	383.00	8.50°	-55.40°	Non
Reflex	386.00	10.10°	-55.40°	Non
Reflex	389.00	9.30°	-55.40°	Non
Reflex	392.00	9.60°	-55.40°	Non
Reflex	395.00	10.10°	-55.40°	Non
Reflex	398.00	9.80°	-55.40°	Non
Reflex	401.00	8.80°	-55.40°	Non
Reflex	404.00	9.60°	-55.40°	Non
Reflex	407.00	10.10°	-55.40°	Non
Reflex	410.00	7.40°	-55.40°	Non
Reflex	413.00	3.80°	-55.40°	Non
Reflex	416.00	5.40°	-55.30°	Non
Reflex	419.00	7.30°	-55.20°	Non
Reflex	422.00	8.30°	-55.30°	Non
Reflex	425.00	10.60°	-55.30°	Non
Reflex	428.00	8.90°	-55.30°	Non
Reflex	431.00	10.40°	-55.30°	Non
Reflex	434.00	7.90°	-55.30°	Non
Reflex	437.00	9.20°	-55.30°	Non
Reflex	440.00	10.10°	-55.40°	Non
Reflex	443.00	11.10°	-55.40°	Non
Reflex	446.00	10.70°	-55.40°	Non
Reflex	449.00	11.40°	-55.40°	Non
Reflex	452.00	10.30°	-55.40°	Non
Reflex	455.00	10.60°	-55.40°	Non
Reflex	458.00	9.90°	-55.40°	Non
Reflex	461.00	8.10°	-55.50°	Non
Reflex	464.00	12.10°	-55.50°	Non
Reflex	467.00	12.60°	-55.50°	Non
Reflex	470.00	12.60°	-55.50°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	473.00	9.30°	-54.10°	Oui					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT						
		<b>Mort-terrain</b>						
2.20	39.00	BA; AMY	2.20	3.50	D003165	1.30	0.005	0.005
		<b>Basalte; Amygdalaire</b>						
		microlitique, légèrement cisailé, amydules carbonatés mm-cm ou de	3.50	5.00	D003166	1.50	0.010	0.010
		QZ mm, localement alternance de passage séricitisé induré et	5.00	6.50	D003167	1.50	0.005	0.005
		chloritisé plus moue contact 60° ac, altération en calcite, cheveux et	6.50	8.00	D003168	1.50	0.006	0.006
		veinules localement // cisaillement 30-40° ac, PY fine irrég diss	8.00	9.50	D003169	1.50	<0.005	0.001
			9.50	11.00	D003170	1.50	<0.005	0.001
			11.00	12.50	D003171	1.50	0.006	0.006
			12.50	13.60	D003172	1.10	0.005	0.005
			13.60	15.10	D003173	1.50	0.005	0.005
			15.10	16.50	D003175	1.40	<0.005	0.001
			16.50	18.00	D003176	1.50	<0.005	0.001
			18.00	19.50	D003177	1.50	0.005	0.005
			19.50	20.60	D003178	1.10	0.005	0.005
			20.60	21.70	D003179	1.10	0.006	0.006
			21.70	23.00	D003180	1.30	0.009	0.009
			23.00	24.60	D003181	1.60	<0.005	0.001
			24.60	26.00	D003182	1.40	0.009	0.009
			26.00	27.30	D003183	1.30	0.008	0.008
			27.30	28.50	D003185	1.20	0.005	0.005
			28.50	30.00	D003186	1.50	0.005	0.005
			30.00	31.50	D003187	1.50	0.007	0.007
			31.50	32.90	D003188	1.40	0.005	0.005
			32.90	34.50	D003189	1.60	0.006	0.006
			34.50	35.50	D003190	1.00	0.005	0.005
			35.50	37.00	D003191	1.50	<0.005	0.001
			37.00	38.00	D003192	1.00	0.005	0.005
			38.00	39.00	D003193	1.00	<0.005	0.001
39.00	48.20	TU; FIN; LAM; AMY	39.00	40.50	D003195	1.50	<0.005	0.001
		<b>Tuf à blocs intermédiaire 60°; Grains fins; Laminations</b>						
		<b>parallèles; Amygdalaire</b>	40.50	42.00	D003196	1.50	<0.005	0.001
		légèrement cisailé, bloc 2-3 cm séricitisé, fragments mm- cm, lamines	42.00	43.50	D003197	1.50	<0.005	0.001
		séricitisé, CL+++ , SR++	43.50	45.00	D003198	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
48.20	66.80	BA; AMY <b>Basalte 50°; Amygdalaire</b> microlitique, légèrement cisailé 30-40° ac, altération en calcite, amygdules de QZ et carbonâtes mm-cm, CL+++ , SR+, leucoxènes, PY fine irrég diss	45.00	46.50	D003199	1.50	0.005		0.005
			46.50	48.20	D003200	1.70	<0.005		0.001
			48.20	49.50	D003202	1.30	<0.005		0.001
			49.50	51.00	D003203	1.50	<0.005		0.001
			51.00	52.50	D003205	1.50	<0.005		0.001
			52.50	54.00	D003206	1.50	0.006		0.006
			54.00	55.50	D003207	1.50	0.007		0.007
			55.50	57.00	D003208	1.50	0.007		0.007
56.60	56.70	FAI <b>Faille 40°</b>	57.00	58.50	D003209	1.50	<0.005		0.001
			58.50	60.00	D003210	1.50	0.006		0.006
			60.00	61.50	D003211	1.50	<0.005		0.001
			61.50	63.00	D003212	1.50	0.020		0.020
			63.00	64.50	D003213	1.50	0.005		0.005
			64.50	65.80	D003215	1.30	<0.005		0.001
			65.80	66.80	D003216	1.00	<0.005		0.001
66.80	71.00	SY; MAS; MTY; FIN <b>Syénite 55°; Roche massive; Grains moyens; Grains fins</b> grenue, altération en calcite, quelques phénocristaux de FP mm, hématisation, séricitisation, PY fine diss	66.80	68.00	D003217	1.20	<0.005		0.001
			68.00	69.50	D003218	1.50	<0.005		0.001
			69.50	71.00	D003219	1.50	<0.005		0.001
71.00	77.00	TU; COU; FIN <b>Tuf à blocs mafique 50°; Coussiné; Grains fins</b> altération en calcite, blocs de 1-2 cm, coussin de basalte amygdulaire séricitisé ±1-15 cm, cisaillement 40-50° ac localement schisteuse, CL++, SR++, amygdules de QZ hématisé, PY fine irrég diss	71.00	72.50	D003220	1.50	<0.005		0.001
			72.50	74.00	D003221	1.50	<0.005		0.001
			74.00	75.50	D003222	1.50	<0.005		0.001
			75.50	77.00	D003223	1.50	<0.005		0.001
77.00	93.50	BA; AMY <b>Basalte 70°; Amygdalaire</b> microlitique, légèrement cisailé, amygdules de QZ ou carbonâtes hématisé, cheveux 30-40° ac, séricite, CL++, PY fine diss	77.00	78.50	D003225	1.50	<0.005		0.001
			78.50	80.00	D003226	1.50	<0.005		0.001
			80.00	81.50	D003227	1.50	<0.005		0.001
			81.50	83.00	D003228	1.50	<0.005		0.001
			83.00	84.00	D003229	1.00	0.005		0.005
			84.00	85.00	D003230	1.00	<0.005		0.001
			85.00	86.10	D003231	1.10	<0.005		0.001
			86.10	87.10	D003232	1.00	<0.005		0.001
			87.10	88.10	D003233	1.00	0.005		0.005
			88.10	89.50	D003235	1.40	<0.005		0.001
			89.50	91.00	D003236	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
93.50	476.00	SY; FIN; MTY <b>Syénite 30°; Grains fins; Grains moyens</b> grenue, localement bréchique à sub bréchique, passage légèrement cisailé sérictisé, qlq phénocristaux de FP automorphe à sub automorphe diss, calcite, sérécite, biotite, HM+++ ,CL+, oxydes de carbonâtes, passage légèrement silicifié, PY fine diss	91.00	92.50	D003237	1.50	0.005		0.005
			92.50	93.50	D003238	1.00	0.028		0.028
			93.50	95.00	D003239	1.50	0.011		0.011
			95.00	96.50	D003240	1.50	0.020		0.020
			96.50	98.00	D003242	1.50	0.495		0.495
			98.00	99.50	D003243	1.50	0.016		0.016
			99.50	101.00	D003245	1.50	0.005		0.005
			101.00	102.50	D003246	1.50	0.135		0.135
			102.50	104.00	D003247	1.50	0.074		0.074
			104.00	105.50	D003248	1.50	0.029		0.029
			105.50	107.00	D003249	1.50	0.046		0.046
107.00	108.50	D003250	1.50	0.026		0.026			
108.40	108.50	FAI <b>Faille 50°</b>	108.50	110.00	D003251	1.50	0.019		0.019
110.00	123.50	SY; FIN; MOY; POR <b>Syénite; Grains fins; Grains moyens; Porphyrique</b> phénocristaux de FP automorphe ou bsub arrondi 0.5-2 cm, + calcite, HM+++ , BO+, SR+	110.00	111.50	D003252	1.50	0.060		0.060
			111.50	113.00	D003253	1.50	0.331		0.331
112.80	112.90	FAI <b>Faille 50°</b> boue verdâtre et fragments mm-cm	113.00	114.50	D003255	1.50	0.136		0.136
			114.50	116.00	D003256	1.50	0.067		0.067
			116.00	117.50	D003257	1.50	0.063		0.063
			117.50	119.00	D003258	1.50	0.063		0.063
			119.00	120.50	D003259	1.50	0.060		0.060
			120.50	122.00	D003260	1.50	0.482		0.482
			122.00	123.50	D003261	1.50	0.170		0.170
			123.50	125.00	D003262	1.50	0.121		0.121
			125.00	126.50	D003263	1.50	0.107		0.107
			126.50	128.00	D003265	1.50	0.262		0.262
			128.00	129.50	D003266	1.50	0.019		0.019
			129.50	131.00	D003267	1.50	0.057		0.057
			131.00	132.50	D003268	1.50	0.052		0.052
132.50	134.00	D003269	1.50	0.006		0.006			
134.00	135.50	D003270	1.50	0.005		0.005			
135.50	137.00	D003271	1.50	0.331		0.331			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	137.00	138.50	D003272	1.50	0.032		0.032
	138.50	140.00	D003273	1.50	0.016		0.016
	140.00	141.50	D003275	1.50	0.007		0.007
	141.50	143.00	D003276	1.50	0.024		0.024
	143.00	144.50	D003277	1.50	0.024		0.024
	144.50	146.00	D003278	1.50	0.011		0.011
	146.00	147.50	D003279	1.50	0.008		0.008
	147.50	149.00	D003280	1.50	0.010		0.010
	149.00	150.50	D003282	1.50	0.035		0.035
	150.50	152.00	D003283	1.50	0.012		0.012
	152.00	153.50	D003285	1.50	0.074		0.074
	153.50	155.00	D003286	1.50	0.031		0.031
	155.00	156.50	D003287	1.50	0.089		0.089
	156.50	158.00	D003288	1.50	0.118		0.118
	158.00	159.50	D003289	1.50	0.506		0.506
	159.50	160.60	D003290	1.10	1.675		1.675
	160.60	162.00	D003291	1.40	1.530		1.530
	162.00	163.50	D003292	1.50	0.286		0.286
	163.50	165.00	D003293	1.50	0.161		0.161
	165.00	166.50	D003295	1.50	1.240		1.240
	166.50	168.00	D003296	1.50	0.170		0.170
	168.00	169.50	D003297	1.50	0.101		0.101
	169.50	171.00	D003298	1.50	0.111		0.111
	171.00	172.50	D003299	1.50	0.094		0.094
	172.50	174.00	D003300	1.50	0.315		0.315
	174.00	175.50	D003301	1.50	0.122		0.122
	175.50	177.00	D003302	1.50	0.196		0.196
	177.00	178.50	D003303	1.50	0.092		0.092
	178.50	180.00	D003305	1.50	0.206		0.206
	180.00	181.30	D003306	1.30	3.200		3.200
	181.30	182.50	D003307	1.20	0.720		0.720
	182.50	184.00	D003308	1.50	0.122		0.122
	184.00	185.50	D003309	1.50	0.053		0.053

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			185.50	187.00	D003310	1.50		0.016	0.016
			187.00	188.50	D003311	1.50		0.006	0.006
			188.50	190.00	D003312	1.50		0.025	0.025
			190.00	191.50	D003313	1.50		0.234	0.234
			191.50	193.00	D003314	1.50		0.133	0.133
			193.00	194.00	D003315	1.00		0.005	0.005
			194.00	195.50	D003316	1.50		0.005	0.005
			195.50	197.00	D003317	1.50		<0.005	0.001
			197.00	198.50	D003318	1.50		0.005	0.005
198.50	200.00	CIS	198.50	200.00	D003319	1.50		0.324	0.324
		<b>Cisaillement 30°</b>	200.00	201.00	D003320	1.00		0.083	0.083
		fragments cm chloritisé et séricitisé	201.00	202.30	D003322	1.30		0.006	0.006
202.30	203.70	CIS	202.30	203.60	D003323	1.30		0.177	0.177
		<b>Cisaillement 40°</b>	203.60	205.00	D003325	1.40		0.013	0.013
			205.00	206.50	D003326	1.50		0.348	0.348
205.50	205.60	FAI	206.50	208.00	D003327	1.50		0.635	0.635
		<b>Faille 30°</b>							
		boue verdâtre							
207.90	208.10	FAI	208.00	209.50	D003328	1.50		0.015	0.015
		<b>Faille 20°</b>							
		faille 10-30° ac boue verdâtre et fragments cm							
209.40	209.60	FAI	209.50	211.00	D003329	1.50		0.022	0.022
		<b>Faille 30°</b>	211.00	212.50	D003330	1.50		0.058	0.058
		boue verdâtre							
212.30	216.00	CIS	212.50	214.00	D003331	1.50		0.017	0.017
		<b>Cisaillement 30°</b>	214.00	215.50	D003332	1.50		0.094	0.094
			215.50	217.00	D003333	1.50		0.072	0.072
			217.00	218.50	D003335	1.50		0.009	0.009
			218.50	220.00	D003336	1.50		<0.005	0.001
			220.00	221.50	D003337	1.50		<0.005	0.001
			221.50	223.00	D003338	1.50		<0.005	0.001
			223.00	224.50	D003339	1.50		0.022	0.022
			224.50	226.00	D003340	1.50		0.028	0.028
			226.00	227.50	D003341	1.50		0.221	0.221



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
247.30	257.50	SY; MAS; MOY; POR <b>Syénite; Roche massive; Grains moyens; Porphyrique</b> phénocristaux 0.5-2 cm automorphe ou sub arrondi, CL+, HM+++; BO+, altération en calcite, PY fine diss	227.50	229.00	D003342	1.50	0.243		0.243
			229.00	230.50	D003343	1.50	0.108		0.108
			230.50	232.00	D003345	1.50	0.101		0.101
			232.00	233.50	D003346	1.50	0.010		0.010
			233.50	235.00	D003347	1.50	0.041		0.041
			235.00	236.50	D003348	1.50	0.006		0.006
			236.50	238.00	D003349	1.50	0.038		0.038
			238.00	239.50	D003350	1.50	0.112		0.112
			239.50	240.50	D003351	1.00	0.092		0.092
			240.50	241.50	D003352	1.00	1.720		1.720
			241.50	242.50	D003353	1.00	0.005		0.005
			242.50	244.00	D003355	1.50	0.005		0.005
			244.00	245.50	D003356	1.50	0.021		0.021
			245.50	247.00	D003357	1.50	<0.005		0.001
			247.00	248.50	D003358	1.50	<0.005		0.001
			248.50	250.00	D003359	1.50	<0.005		0.001
			250.00	251.50	D003360	1.50	0.062		0.062
			251.50	253.00	D003362	1.50	0.006		0.006
			253.00	254.50	D003363	1.50	0.005		0.005
			254.50	256.00	D003365	1.50	0.010		0.010
			256.00	257.50	D003366	1.50	<0.005		0.001
			257.50	259.00	D003367	1.50	0.128		0.128
			259.00	260.50	D003368	1.50	0.187		0.187
			260.50	262.00	D003369	1.50	0.068		0.068
			262.00	263.50	D003370	1.50	0.008		0.008
			263.50	265.00	D003371	1.50	0.015		0.015
			265.00	266.50	D003372	1.50	0.080		0.080
			266.50	268.00	D003373	1.50	<0.005		0.001
268.00	269.50	D003375	1.50	0.005		0.005			
269.50	271.00	D003376	1.50	<0.005		0.001			
271.00	272.50	D003377	1.50	<0.005		0.001			
272.50	274.00	D003378	1.50	0.038		0.038			
274.00	275.50	D003379	1.50	0.028		0.028			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	275.50	277.00	D003380	1.50	0.008		0.008
	277.00	278.50	D003381	1.50	<0.005		0.001
	278.50	280.00	D003382	1.50	0.006		0.006
	280.00	281.50	D003383	1.50	0.006		0.006
	281.50	283.00	D003385	1.50	0.076		0.076
	283.00	284.50	D003386	1.50	0.245		0.245
	284.50	286.00	D003387	1.50	0.115		0.115
	286.00	287.50	D003388	1.50	0.250		0.250
	287.50	289.00	D003389	1.50	0.027		0.027
	289.00	290.50	D003390	1.50	0.012		0.012
	290.50	292.00	D003391	1.50	0.145		0.145
	292.00	293.50	D003392	1.50	0.013		0.013
	293.50	295.00	D003393	1.50	0.011		0.011
	295.00	296.50	D003395	1.50	0.007		0.007
	296.50	298.00	D003396	1.50	0.010		0.010
	298.00	299.50	D003397	1.50	0.336		0.336
	299.50	301.00	D003398	1.50	0.051		0.051
	301.00	302.60	D003399	1.60	0.877		0.877
	302.60	304.00	D003400	1.40	0.008		0.008
	304.00	305.50	D003402	1.50	0.015		0.015
	305.50	307.00	D003403	1.50	0.006		0.006
	307.00	308.50	D003405	1.50	0.009		0.009
	308.50	310.00	D003406	1.50	<0.005		0.001
	310.00	311.50	D003407	1.50	0.020		0.020
	311.50	312.50	D003408	1.00	0.008		0.008
	312.50	314.00	D003409	1.50	0.005		0.005
	314.00	315.50	D003410	1.50	<0.005		0.001
	315.50	317.00	D003411	1.50	0.006		0.006
	317.00	318.50	D003412	1.50	0.005		0.005
	318.50	320.00	D003413	1.50	0.014		0.014
	320.00	321.50	D003415	1.50	0.006		0.006
	321.50	323.00	D003416	1.50	0.010		0.010
	323.00	324.50	D003417	1.50	0.049		0.049

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	324.50	326.00	D003418	1.50	0.212		0.212
	326.00	327.50	D003419	1.50	0.077		0.077
	327.50	329.00	D003420	1.50	0.005		0.005
	329.00	330.50	D003421	1.50	0.010		0.010
	330.50	332.00	D003422	1.50	0.008		0.008
	332.00	333.50	D003423	1.50	<0.005		0.001
	333.50	334.70	D003425	1.20	0.008		0.008
	334.70	336.00	D003426	1.30	0.587		0.587
	336.00	337.50	D003427	1.50	0.033		0.033
	337.50	339.00	D003428	1.50	1.175		1.175
	339.00	340.50	D003429	1.50	0.189		0.189
	340.50	342.00	D003430	1.50	0.277		0.277
	342.00	343.50	D003431	1.50	0.309		0.309
	343.50	345.00	D003432	1.50	0.280		0.280
	345.00	346.50	D003433	1.50	1.195		1.195
	346.50	348.00	D003435	1.50	0.615		0.615
	348.00	349.50	D003436	1.50	0.136		0.136
	349.50	351.00	D003437	1.50	0.152		0.152
	351.00	352.50	D003438	1.50	0.058		0.058
	352.50	354.00	D003439	1.50	0.312		0.312
	354.00	355.50	D003440	1.50	0.041		0.041
	355.50	357.00	D003442	1.50	0.251		0.251
	357.00	358.50	D003443	1.50	0.109		0.109
	358.50	360.00	D003445	1.50	0.066		0.066
	360.00	361.50	D003446	1.50	0.028		0.028
	361.50	363.00	D003447	1.50	0.033		0.033
	363.00	364.50	D003448	1.50	0.074		0.074
	364.50	366.00	D003449	1.50	0.129		0.129
	366.00	367.50	D003450	1.50	0.184		0.184
	367.50	369.00	D003451	1.50	0.138		0.138
	369.00	370.50	D003452	1.50	0.100		0.100
	370.50	372.00	D003453	1.50	0.010		0.010
	372.00	373.50	D003455	1.50	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	373.50	375.00	D003456	1.50	0.027		0.027
	375.00	376.50	D003457	1.50	0.187		0.187
	376.50	378.00	D003458	1.50	0.061		0.061
	378.00	379.50	D003459	1.50	0.192		0.192
	379.50	381.00	D003460	1.50	0.138		0.138
	381.00	382.50	D003461	1.50	0.052		0.052
	382.50	384.00	D003462	1.50	0.112		0.112
	384.00	385.50	D003463	1.50	0.008		0.008
	385.50	387.00	D003465	1.50	0.010		0.010
	387.00	388.50	D003466	1.50	0.009		0.009
	388.50	390.00	D003467	1.50	0.007		0.007
	390.00	391.50	D003468	1.50	0.013		0.013
	391.50	393.00	D003469	1.50	0.008		0.008
	393.00	394.50	D003470	1.50	0.021		0.021
	394.50	396.00	D003471	1.50	0.017		0.017
	396.00	397.50	D003472	1.50	0.107		0.107
	397.50	399.00	D003473	1.50	0.007		0.007
	399.00	400.50	D003475	1.50	0.011		0.011
	400.50	402.00	D003476	1.50	<0.005		0.001
	402.00	403.50	D003477	1.50	<0.005		0.001
	403.50	405.00	D003478	1.50	0.006		0.006
	405.00	406.50	D003479	1.50	<0.005		0.001
	406.50	408.00	D003480	1.50	0.005		0.005
	408.00	409.50	D003482	1.50	0.022		0.022
	409.50	411.00	D003483	1.50	0.008		0.008
	411.00	412.50	D003485	1.50	0.006		0.006
	412.50	413.60	D003486	1.10	0.019		0.019
	413.60	415.00	D003487	1.40	0.943		0.943
	415.00	416.00	D003488	1.00	0.048		0.048
	416.00	417.50	D003489	1.50	0.006		0.006
	417.50	419.00	D003490	1.50	0.025		0.025
	419.00	420.50	D003491	1.50	1.630		1.630
	420.50	422.00	D003492	1.50	0.336		0.336

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			422.00	423.50	D003493	1.50		0.007		0.007
			423.50	425.00	D003495	1.50		0.007		0.007
			425.00	426.50	D003496	1.50		0.067		0.067
			426.50	428.00	D003497	1.50		0.017		0.017
			428.00	429.50	D003498	1.50		0.028		0.028
			429.50	431.00	D003499	1.50		0.007		0.007
			431.00	432.50	D003500	1.50		0.023		0.023
			432.50	434.00	D003501	1.50		0.056		0.056
433.40	433.70	FRC Fracturé fragments cm	434.00	435.50	D003502	1.50		0.065		0.065
			435.50	437.00	D003503	1.50		0.046		0.046
			437.00	438.50	D003505	1.50		0.067		0.067
			438.50	440.00	D003506	1.50		0.028		0.028
			440.00	441.50	D003507	1.50		<0.005		0.001
			441.50	443.00	D003508	1.50		0.017		0.017
			443.00	444.50	D003509	1.50		0.048		0.048
			444.50	446.00	D003510	1.50		<0.005		0.001
			446.00	447.50	D003511	1.50		<0.005		0.001
			447.50	449.00	D003512	1.50		<0.005		0.001
			449.00	450.50	D003513	1.50		<0.005		0.001
			450.50	452.00	D003515	1.50		<0.005		0.001
			452.00	453.50	D003516	1.50		<0.005		0.001
			453.50	455.00	D003517	1.50		<0.005		0.001
			455.00	456.50	D003518	1.50		0.213		0.213
			456.50	458.00	D003519	1.50		0.233		0.233
			458.00	459.50	D003520	1.50		<0.005		0.001
			459.50	461.00	D003522	1.50		0.023		0.023
			461.00	462.50	D003523	1.50		<0.005		0.001
			462.50	464.00	D003525	1.50		0.009		0.009
			464.00	465.50	D003526	1.50		0.113		0.113
			465.50	467.00	D003527	1.50		0.014		0.014
			467.00	468.50	D003528	1.50		0.008		0.008
			468.50	470.00	D003529	1.50		<0.005		0.001
			470.00	471.50	D003530	1.50		0.017		0.017

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	471.50	473.00	D003531	1.50	0.016		0.016
	473.00	474.50	D003532	1.50	0.005		0.005
	474.50	476.00	D003533	1.50	0.005		0.005
<p>476.00 Fin du sondage            Nombre d'échantillons : 325            Nombre d'échantillons QAQC : 44            Longueur totale échantillonnée : 473.80</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.60	15.10	D003174	D003173	1.50	<0.005	0.001
26.00	26.00	D003184	A3	0.00	0.615	0.615
38.00	39.00	D003194	D003193	1.00	0.005	0.005
46.50	46.50	D003201	M1	0.00	<0.005	0.001
49.50	49.50	D003204	B4	0.00	2.650	2.650
63.00	64.50	D003214	D003213	1.50	0.005	0.005
75.50	75.50	D003224	C4	0.00	1.330	1.330
87.10	88.10	D003234	D003233	1.00	<0.005	0.001
95.00	95.00	D003241	M1	0.00	<0.005	0.001
98.00	98.00	D003244	D2	0.00	0.835	0.835
111.50	113.00	D003254	D003253	1.50	0.332	0.332
125.00	125.00	D003264	F2	0.00	8.540	8.540
138.50	140.00	D003274	D003273	1.50	0.041	0.041
147.50	147.50	D003281	M1	0.00	<0.005	0.001
150.50	150.50	D003284	G2	0.00	3.890	3.890
163.50	165.00	D003294	D003293	1.50	0.167	0.167
177.00	177.00	D003304	H	0.00	0.956	0.956
200.00	200.00	D003321	M1	0.00	<0.005	0.001
202.30	202.30	D003324	A3	0.00	0.600	0.600
215.50	217.00	D003334	D003333	1.50	0.085	0.085
229.00	229.00	D003344	B4	0.00	2.560	2.560
241.50	242.50	D003354	D003353	1.00	0.007	0.007
250.00	250.00	D003361	M1	0.00	<0.005	0.001
253.00	253.00	D003364	C4	0.00	1.320	1.320
266.50	268.00	D003374	D003373	1.50	<0.005	0.001
280.00	280.00	D003384	D2	0.00	0.851	0.851
293.50	295.00	D003394	D003393	1.50	0.014	0.014
302.60	302.60	D003401	M1	0.00	<0.005	0.001
305.50	305.50	D003404	G2	0.00	3.990	3.990
318.50	320.00	D003414	D003413	1.50	0.012	0.012
332.00	332.00	D003424	F2	0.00	8.330	8.330
345.00	346.50	D003434	D003433	1.50	1.260	1.260
354.00	354.00	D003441	M1	0.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
357.00	357.00	D003444	H	0.00	0.991	0.991
370.50	372.00	D003454	D003453	1.50	0.012	0.012
384.00	384.00	D003464	A3	0.00	0.587	0.587
397.50	399.00	D003474	D003473	1.50	0.011	0.011
406.50	406.50	D003481	M1	0.00	0.005	0.005
409.50	409.50	D003484	B4	0.00	2.650	2.650
422.00	423.50	D003494	D003493	1.50	0.013	0.013
435.50	435.50	D003504	C4	0.00	1.400	1.400
449.00	450.50	D003514	D003513	1.50	<0.005	0.001
458.00	458.00	D003521	M1	0.00	<0.005	0.001
461.00	461.00	D003524	D2	0.00	0.694	0.694



## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-160</b>	Titre minier :	Section :	631000
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-04-11	Date de description :	2010-05-15
	Au : 2010-04-18		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 464.00 m

UTM

Est	630 999.9
Nord	5 374 200.4
Élévation	304.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	357.90°	-59.00°	Non
Reflex	5.00	359.70°	-60.00°	Non
Reflex	8.00	358.20°	-59.80°	Non
Reflex	11.00	1.70°	-58.60°	Non
Reflex	14.00	4.30°	-59.10°	Oui
Reflex	17.00	1.70°	-59.10°	Non
Reflex	20.00	1.50°	-58.60°	Non
Reflex	23.00	0.90°	-58.30°	Non
Reflex	26.00	0.70°	-58.00°	Non
Reflex	29.00	0.60°	-57.70°	Non
Reflex	32.00	0.10°	-57.40°	Non
Reflex	35.00	0.10°	-57.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.40°	-56.60°	Non
Reflex	41.00	359.10°	-56.30°	Non
Reflex	44.00	359.60°	-56.00°	Non
Reflex	47.00	359.30°	-55.50°	Non
Reflex	50.00	0.80°	-52.90°	Non
Reflex	53.00	358.90°	-54.70°	Non
Reflex	56.00	359.40°	-54.30°	Non
Reflex	59.00	359.40°	-54.00°	Non
Reflex	62.00	358.90°	-53.90°	Non
Reflex	65.00	359.30°	-53.80°	Non
Reflex	68.00	359.00°	-53.60°	Non
Reflex	71.00	359.10°	-53.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	358.90°	-53.10°	Non	Reflex	173.00	2.20°	-51.50°	Non
Reflex	77.00	358.70°	-52.80°	Non	Reflex	176.00	2.40°	-51.50°	Non
Reflex	80.00	358.20°	-52.60°	Non	Reflex	179.00	2.40°	-51.50°	Non
Reflex	83.00	358.10°	-52.10°	Non	Reflex	182.00	2.50°	-51.50°	Non
Reflex	86.00	357.60°	-51.70°	Non	Reflex	185.00	3.80°	-52.20°	Non
Reflex	89.00	357.50°	-51.60°	Non	Reflex	188.00	2.90°	-51.20°	Non
Reflex	92.00	358.10°	-51.40°	Non	Reflex	191.00	3.40°	-51.20°	Non
Reflex	95.00	357.90°	-51.30°	Non	Reflex	194.00	2.50°	-51.00°	Non
Reflex	98.00	357.40°	-51.10°	Non	Reflex	197.00	3.10°	-51.00°	Non
Reflex	101.00	357.60°	-51.10°	Non	Reflex	200.00	3.10°	-51.00°	Non
Reflex	104.00	358.20°	-50.90°	Non	Reflex	203.00	3.70°	-50.90°	Non
Reflex	107.00	358.30°	-50.80°	Non	Reflex	206.00	3.40°	-50.80°	Non
Reflex	110.00	358.40°	-51.30°	Non	Reflex	209.00	3.20°	-50.80°	Non
Reflex	113.00	358.80°	-50.80°	Non	Reflex	212.00	3.10°	-50.70°	Non
Reflex	116.00	359.30°	-50.90°	Non	Reflex	215.00	3.00°	-50.70°	Non
Reflex	119.00	359.40°	-51.00°	Non	Reflex	218.00	3.00°	-50.70°	Non
Reflex	122.00	359.50°	-51.00°	Non	Reflex	221.00	3.20°	-50.60°	Non
Reflex	125.00	359.80°	-51.10°	Non	Reflex	224.00	3.20°	-50.50°	Non
Reflex	128.00	359.80°	-51.30°	Non	Reflex	227.00	3.10°	-50.50°	Non
Reflex	131.00	0.60°	-51.30°	Non	Reflex	230.00	3.00°	-50.40°	Non
Reflex	134.00	359.90°	-51.30°	Non	Reflex	233.00	3.40°	-50.40°	Non
Reflex	137.00	1.50°	-51.30°	Non	Reflex	236.00	3.30°	-50.30°	Non
Reflex	140.00	0.60°	-51.40°	Non	Reflex	239.00	3.00°	-50.30°	Non
Reflex	143.00	0.50°	-51.30°	Non	Reflex	242.00	3.10°	-50.20°	Non
Reflex	146.00	2.10°	-51.40°	Oui	Reflex	245.00	3.10°	-50.20°	Non
Reflex	149.00	1.20°	-51.50°	Non	Reflex	248.00	2.80°	-50.10°	Non
Reflex	152.00	1.60°	-51.50°	Non	Reflex	251.00	2.50°	-50.10°	Non
Reflex	155.00	0.40°	-51.40°	Non	Reflex	254.00	2.30°	-49.90°	Non
Reflex	158.00	1.20°	-51.50°	Non	Reflex	257.00	2.00°	-49.80°	Non
Reflex	161.00	1.40°	-51.50°	Non	Reflex	260.00	2.30°	-49.60°	Non
Reflex	164.00	1.90°	-51.70°	Non	Reflex	263.00	2.50°	-49.60°	Non
Reflex	167.00	2.10°	-51.50°	Non	Reflex	266.00	2.70°	-49.60°	Non
Reflex	170.00	2.20°	-51.50°	Non	Reflex	269.00	1.10°	-49.60°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	0.60°	-49.50°	Non	Reflex	371.00	8.50°	-48.40°	Non
Reflex	275.00	0.60°	-49.60°	Non	Reflex	374.00	4.10°	-48.40°	Oui
Reflex	278.00	1.50°	-49.50°	Non	Reflex	377.00	8.30°	-48.40°	Non
Reflex	281.00	2.50°	-49.40°	Non	Reflex	380.00	7.50°	-48.30°	Non
Reflex	284.00	3.20°	-49.30°	Non	Reflex	383.00	7.50°	-48.20°	Non
Reflex	287.00	3.90°	-49.30°	Non	Reflex	386.00	2.70°	-48.20°	Non
Reflex	290.00	3.90°	-49.30°	Non	Reflex	389.00	5.70°	-48.10°	Non
Reflex	293.00	4.60°	-49.20°	Non	Reflex	392.00	4.50°	-48.00°	Non
Reflex	296.00	4.10°	-49.20°	Non	Reflex	395.00	8.30°	-48.00°	Non
Reflex	299.00	6.80°	-49.20°	Oui	Reflex	398.00	4.50°	-48.00°	Non
Reflex	302.00	5.50°	-49.10°	Non	Reflex	401.00	5.20°	-48.00°	Non
Reflex	305.00	6.30°	-49.10°	Non	Reflex	404.00	5.90°	-48.00°	Non
Reflex	308.00	8.30°	-49.00°	Non	Reflex	407.00	6.80°	-48.00°	Non
Reflex	311.00	7.50°	-49.00°	Non	Reflex	410.00	7.40°	-47.90°	Non
Reflex	314.00	6.00°	-49.00°	Non	Reflex	413.00	8.70°	-48.00°	Non
Reflex	317.00	3.80°	-49.00°	Non	Reflex	416.00	7.20°	-48.00°	Non
Reflex	320.00	5.00°	-48.90°	Non	Reflex	419.00	6.10°	-48.00°	Non
Reflex	323.00	6.70°	-48.90°	Non	Reflex	422.00	9.70°	-48.10°	Non
Reflex	326.00	5.30°	-48.90°	Oui	Reflex	425.00	10.10°	-48.10°	Non
Reflex	329.00	7.60°	-48.90°	Non	Reflex	428.00	9.50°	-48.10°	Non
Reflex	332.00	6.90°	-48.80°	Non	Reflex	431.00	10.20°	-48.00°	Non
Reflex	335.00	8.30°	-48.70°	Non	Reflex	434.00	11.00°	-48.00°	Non
Reflex	338.00	4.10°	-48.70°	Oui	Reflex	437.00	12.70°	-48.00°	Non
Reflex	341.00	8.60°	-48.70°	Non	Reflex	440.00	11.20°	-47.90°	Non
Reflex	344.00	8.30°	-48.70°	Non	Reflex	443.00	10.50°	-47.70°	Non
Reflex	347.00	9.50°	-48.60°	Non	Reflex	446.00	11.50°	-47.70°	Non
Reflex	350.00	7.80°	-48.40°	Oui	Reflex	449.00	11.10°	-47.50°	Non
Reflex	353.00	9.90°	-48.40°	Non	Reflex	452.00	10.60°	-47.40°	Non
Reflex	356.00	8.60°	-48.40°	Non	Reflex	455.00	8.20°	-47.40°	Non
Reflex	359.00	9.20°	-48.40°	Non	Reflex	458.00	7.90°	-47.20°	Non
Reflex	362.00	8.40°	-48.40°	Non	Reflex	461.00	9.00°	-47.20°	Non
Reflex	365.00	8.90°	-48.40°	Non	Reflex	464.00	10.20°	-47.20°	Non
Reflex	368.00	9.30°	-48.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.00	MT						
		<b>Mort-terrain</b>						
2.00	54.40	BA; MAS; AMY; COU	2.00	3.50	D003534	1.50	0.025	0.025
		<b>Basalte; Roche massive; Amygdalaire; Cousiné</b>	3.50	5.00	D003535	1.50	0.008	0.008
		microlitique, localement cisailé 30-50° ac, oxydes de carbonâtes, SR++, CL+++, amygdules carbonâté, PY automorphe et fine irrég diss	5.00	6.50	D003536	1.50	<0.005	0.001
			6.50	8.00	D003537	1.50	0.006	0.006
			8.00	9.50	D003538	1.50	<0.005	0.001
			9.50	11.00	D003539	1.50	0.005	0.005
			11.00	12.50	D003540	1.50	0.006	0.006
			12.50	14.00	D003541	1.50	0.005	0.005
			14.00	15.50	D003542	1.50	<0.005	0.001
			15.50	17.00	D003544	1.50	0.010	0.010
			17.00	18.50	D003545	1.50	0.007	0.007
			18.50	20.00	D003546	1.50	0.005	0.005
			20.00	21.50	D003547	1.50	<0.005	0.001
			21.50	23.00	D003548	1.50	0.007	0.007
			23.00	24.40	D003549	1.40	0.007	0.007
			24.40	26.00	D003550	1.60	0.108	0.108
			26.00	27.50	D003551	1.50	0.011	0.011
			27.50	29.00	D003552	1.50	<0.005	0.001
			29.00	30.50	D003554	1.50	0.013	0.013
			30.50	32.00	D003555	1.50	0.009	0.009
			32.00	33.50	D003556	1.50	0.295	0.295
			33.50	35.00	D003557	1.50	0.013	0.013
			35.00	36.50	D003558	1.50	0.010	0.010
			36.50	38.00	D003559	1.50	1.830	1.830
			38.00	39.50	D003560	1.50	0.295	0.295
			39.50	41.00	D003561	1.50	0.046	0.046
			41.00	42.50	D003562	1.50	0.107	0.107
			42.50	44.00	D003564	1.50	0.008	0.008
			44.00	45.50	D003565	1.50	0.265	0.265
			45.50	47.00	D003566	1.50	0.199	0.199
			47.00	48.50	D003567	1.50	0.007	0.007
			48.50	50.00	D003568	1.50	0.514	0.514

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
54.40	92.00	BA; MAS; AMY <b>Basalte andésitique 40°; Roche massive; Amygdalaire</b> légèrement induré, jaune verdâtre, localement amygdalaire, séricitisé légèrement chloritisé, EP+, PY en amas et fine irrég diss	50.00	51.50	D003569	1.50	0.008		0.008
			51.50	53.00	D003571	1.50	<0.005		0.001
			53.00	54.40	D003572	1.40	<0.005		0.001
			54.40	56.00	D003574	1.60	0.005		0.005
			56.00	57.40	D003575	1.40	0.136		0.136
			57.40	59.00	D003576	1.60	0.069		0.069
			59.00	60.50	D003577	1.50	0.005		0.005
			60.50	62.00	D003578	1.50	0.006		0.006
			62.00	63.50	D003579	1.50	0.005		0.005
			63.50	65.00	D003580	1.50	0.005		0.005
			65.00	66.50	D003581	1.50	0.005		0.005
			66.50	68.00	D003582	1.50	0.028		0.028
			68.00	69.50	D003584	1.50	<0.005		0.001
			69.50	71.00	D003585	1.50	0.006		0.006
			71.00	72.50	D003586	1.50	<0.005		0.001
			72.50	74.00	D003587	1.50	<0.005		0.001
			74.00	75.50	D003588	1.50	0.005		0.005
			75.50	77.00	D003589	1.50	0.020		0.020
			77.00	78.50	D003590	1.50	0.007		0.007
			78.50	80.00	D003591	1.50	<0.005		0.001
80.00	81.50	D003592	1.50	<0.005		0.001			
81.50	83.00	D003594	1.50	0.007		0.007			
83.00	84.50	D003595	1.50	<0.005		0.001			
84.50	86.00	D003596	1.50	<0.005		0.001			
86.00	87.50	D003597	1.50	0.005		0.005			
87.50	89.00	D003598	1.50	0.007		0.007			
89.00	90.50	D003599	1.50	0.005		0.005			
90.50	92.00	D003600	1.50	0.180		0.180			
92.00	448.70	SY; MAS; FIN <b>Syénite 60°; Roche massive; Grains fins</b> grenue localement bréchique à sub bréchique et altéré en silice, phénocristaux e FP, hématisation, ++calcite, zone de transition avec mélange de syénite basalte ± 92-102.9 m,	92.00	93.50	D003601	1.50	0.021		0.021
			93.50	95.00	D003602	1.50	0.054		0.054
			95.00	96.50	D003604	1.50	0.009		0.009
			96.50	98.00	D003605	1.50	0.052		0.052
			98.00	99.50	D003606	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
102.90	206.00	SY; MAS; FIN; POR <b>Syénite 30°; Roche massive; Grains fins; Porphyrique</b> localement trachytique à phénocristaux de FP 0.2-3 cm sub arrondi ou automorphe 30-50° ac SR+ CL+, HM+++, oxydes de carbonâtes, SR+, PY fine diss	99.50	100.90	D003607	1.40	0.028		0.028
			100.90	101.90	D003608	1.00	0.014		0.014
			101.90	102.90	D003609	1.00	0.013		0.013
			102.90	104.00	D003611	1.10	<0.005		0.001
			104.00	105.50	D003612	1.50	0.842		0.842
			105.50	107.00	D003614	1.50	0.076		0.076
			107.00	108.50	D003615	1.50	0.111		0.111
			108.50	110.00	D003616	1.50	<0.005		0.001
			110.00	111.50	D003617	1.50	0.006		0.006
			111.50	113.00	D003618	1.50	<0.005		0.001
			113.00	114.50	D003619	1.50	<0.005		0.001
			114.50	116.00	D003620	1.50	0.008		0.008
			116.00	117.50	D003621	1.50	0.207		0.207
			117.50	119.00	D003622	1.50	0.299		0.299
			119.00	120.50	D003624	1.50	0.038		0.038
			120.50	122.00	D003625	1.50	0.044		0.044
			122.00	123.50	D003626	1.50	0.018		0.018
			123.50	125.00	D003627	1.50	0.014		0.014
			125.00	126.50	D003628	1.50	0.048		0.048
			126.50	128.00	D003629	1.50	0.057		0.057
128.00	129.50	D003630	1.50	0.030		0.030			
129.50	131.00	D003631	1.50	0.118		0.118			
131.00	132.50	D003632	1.50	0.048		0.048			
132.50	134.00	D003634	1.50	0.010		0.010			
134.00	135.50	D003635	1.50	0.039		0.039			
135.50	137.00	D003636	1.50	0.008		0.008			
137.00	138.50	D003637	1.50	0.049		0.049			
138.50	140.00	D003638	1.50	0.415		0.415			
140.00	141.50	D003639	1.50	0.047		0.047			
141.50	143.00	D003640	1.50	0.030		0.030			
143.00	144.50	D003641	1.50	0.126		0.126			
144.50	146.00	D003642	1.50	0.185		0.185			
146.00	147.50	D003644	1.50	0.143		0.143			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.50	149.00	D003645	1.50	0.185		0.185
	149.00	150.50	D003646	1.50	0.074		0.074
	150.50	152.00	D003647	1.50	0.470		0.470
	152.00	153.50	D003648	1.50	0.083		0.083
	153.50	155.00	D003649	1.50	0.016		0.016
	155.00	156.50	D003651	1.50	0.011		0.011
	156.50	158.00	D003652	1.50	0.031		0.031
	158.00	159.50	D003654	1.50	0.014		0.014
	159.50	161.00	D003655	1.50	0.007		0.007
	161.00	162.50	D003656	1.50	<0.005		0.001
	162.50	164.00	D003657	1.50	0.007		0.007
	164.00	165.50	D003658	1.50	<0.005		0.001
	165.50	167.00	D003659	1.50	0.018		0.018
	167.00	168.50	D003660	1.50	<0.005		0.001
	168.50	170.00	D003661	1.50	0.035		0.035
	170.00	171.50	D003662	1.50	0.126		0.126
	171.50	173.00	D003664	1.50	0.026		0.026
	173.00	174.50	D003665	1.50	8.330		8.330
	174.50	176.00	D003666	1.50	0.088		0.088
	176.00	177.50	D003667	1.50	0.088		0.088
	177.50	179.00	D003668	1.50	0.023		0.023
	179.00	180.50	D003669	1.50	0.027		0.027
	180.50	182.00	D003670	1.50	0.274		0.274
	182.00	183.50	D003671	1.50	0.789		0.789
	183.50	185.00	D003672	1.50	1.510		1.510
	185.00	186.50	D003674	1.50	0.473		0.473
	186.50	188.00	D003675	1.50	0.011		0.011
	188.00	189.50	D003676	1.50	0.109		0.109
	189.50	191.00	D003677	1.50	0.277		0.277
	191.00	192.50	D003678	1.50	0.376		0.376
	192.50	194.00	D003679	1.50	0.126		0.126
	194.00	195.50	D003680	1.50	0.277		0.277
	195.50	197.00	D003681	1.50	1.020		1.020

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			197.00	198.50	D003682	1.50		0.223		0.223
			198.50	200.00	D003684	1.50		1.430		1.430
			200.00	201.50	D003685	1.50		1.765		1.765
			201.50	203.00	D003686	1.50		0.900		0.900
			203.00	204.50	D003687	1.50		0.213		0.213
			204.50	206.00	D003688	1.50		0.440		0.440
			206.00	207.50	D003689	1.50		0.557		0.557
			207.50	209.00	D003691	1.50		0.094		0.094
			209.00	210.50	D003692	1.50		0.006		0.006
			210.50	212.00	D003694	1.50		<0.005		0.001
			212.00	213.50	D003695	1.50		0.343		0.343
			213.50	215.00	D003696	1.50		0.119		0.119
			215.00	216.50	D003697	1.50		0.079		0.079
			216.50	218.00	D003698	1.50		0.016		0.016
			218.00	219.50	D003699	1.50		0.006		0.006
			219.50	221.00	D003700	1.50		0.016		0.016
			221.00	222.50	D003701	1.50		0.393		0.393
			222.50	224.00	D003702	1.50		0.005		0.005
			224.00	225.50	D003704	1.50		0.006		0.006
			225.50	227.00	D003705	1.50		0.005		0.005
			227.00	228.40	D003706	1.40		<0.005		0.001
228.40	235.00	SY; FIN; POR	228.40	230.00	D003707	1.60		0.006		0.006
		<b>Syénite 40°; Grains fins; Porphyrique</b>	230.00	231.50	D003708	1.50		<0.005		0.001
		texture trachytique, phénocristaux de FP automorphe étiré	231.50	233.00	D003709	1.50		<0.005		0.001
		30-50° ac, HM+++ , SR++	233.00	234.00	D003710	1.00		<0.005		0.001
			234.00	235.00	D003711	1.00		0.125		0.125
235.00	246.60	CIS	235.00	236.50	D003712	1.50		0.007		0.007
		<b>Cisaillement 50°</b>	236.50	238.00	D003714	1.50		0.009		0.009
			238.00	239.50	D003715	1.50		0.005		0.005
			239.50	241.00	D003716	1.50		0.190		0.190
			241.00	242.50	D003717	1.50		0.009		0.009
			242.50	244.00	D003718	1.50		0.007		0.007
			244.00	245.50	D003719	1.50		0.612		0.612



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
250.00	256.00	CIS <b>Cisaillement 40°</b>	245.50	247.00	D003720	1.50	0.679		0.679
			247.00	248.50	D003721	1.50	0.193		0.193
			248.50	250.00	D003722	1.50	0.006		0.006
			250.00	251.50	D003724	1.50	0.008		0.008
			251.50	253.00	D003725	1.50	0.005		0.005
			253.00	254.50	D003726	1.50	0.041		0.041
			254.50	256.00	D003727	1.50	0.046		0.046
256.00	256.10	FAI <b>Faille</b> fragments et boue de faille	256.00	257.50	D003728	1.50	1.300		1.300
			257.50	259.00	D003729	1.50	0.409		0.409
			259.00	260.50	D003731	1.50	0.354		0.354
			260.50	262.00	D003732	1.50	0.065		0.065
			262.00	263.50	D003734	1.50	0.102		0.102
			263.50	265.00	D003735	1.50	0.027		0.027
			265.00	266.50	D003736	1.50	0.194		0.194
			266.50	268.00	D003737	1.50	0.091		0.091
			268.00	269.50	D003738	1.50	0.044		0.044
			269.50	271.00	D003739	1.50	0.041		0.041
272.50	292.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux 0.2-0.7 cm, hématisation, séricitisation, oxydes de carbonâtes, PY fine	271.00	272.50	D003740	1.50	0.314		0.314
			272.50	274.00	D003741	1.50	0.039		0.039
			274.00	275.50	D003742	1.50	0.019		0.019
			275.50	277.00	D003744	1.50	0.014		0.014
			277.00	278.50	D003745	1.50	0.038		0.038
			278.50	280.00	D003746	1.50	0.040		0.040
			280.00	281.50	D003747	1.50	0.012		0.012
			281.50	283.00	D003748	1.50	0.012		0.012
			283.00	284.50	D003749	1.50	0.006		0.006
			284.50	286.00	D003750	1.50	0.012		0.012
			286.00	287.50	D003751	1.50	0.006		0.006
			287.50	289.00	D003752	1.50	0.005		0.005
289.00	290.50	D003754	1.50	<0.005		0.001			
290.50	292.00	D003755	1.50	0.005		0.005			
292.00	293.50	D003756	1.50	<0.005		0.001			
293.50	295.00	D003757	1.50	0.103		0.103			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
316.00	326.50	SY; MAS; POR <b>Syénite; Roche massive; Porphyrique</b> phénocristaux de FP 0.2- 1 cm localement séricitisé, altération en calcite, veines de carbonâtes hématisé, veinules et cheveux de carbonâtes, PY fine irrég diss	295.00	296.50	D003758	1.50	0.006		0.006
			296.50	298.00	D003759	1.50	0.005		0.005
			298.00	299.50	D003760	1.50	0.052		0.052
			299.50	301.00	D003761	1.50	0.680		0.680
			301.00	302.50	D003762	1.50	0.045		0.045
			302.50	304.00	D003764	1.50	0.012		0.012
			304.00	305.50	D003765	1.50	0.012		0.012
			305.50	307.00	D003766	1.50	0.079		0.079
			307.00	308.50	D003767	1.50	0.022		0.022
			308.50	310.00	D003768	1.50	0.009		0.009
			310.00	311.50	D003769	1.50	<0.005		0.001
			311.50	313.00	D003771	1.50	0.005		0.005
			313.00	314.50	D003772	1.50	0.005		0.005
			314.50	316.00	D003774	1.50	0.009		0.009
			316.00	317.50	D003775	1.50	<0.005		0.001
			317.50	319.00	D003776	1.50	<0.005		0.001
			319.00	320.50	D003777	1.50	<0.005		0.001
			320.50	322.00	D003778	1.50	<0.005		0.001
			322.00	323.50	D003779	1.50	<0.005		0.001
			323.50	325.00	D003780	1.50	0.010		0.010
325.00	326.50	D003781	1.50	<0.005		0.001			
326.50	328.00	D003782	1.50	<0.005		0.001			
328.00	329.50	D003784	1.50	<0.005		0.001			
329.50	331.00	D003785	1.50	<0.005		0.001			
331.00	332.50	D003786	1.50	<0.005		0.001			
332.50	334.00	D003787	1.50	0.007		0.007			
334.00	363.00	SY; MAS; POR; MOY <b>Syénite; Roche massive; Porphyrique; Grains moyens</b> phénocristaux automorphe ou sub arrondi blanchâtre ou rosé localement maclé 0.3-2 cm, passablement altéré en silice, +++calcite, HM++, CL++, BO++. PY fine diss	334.00	335.50	D003788	1.50	0.013		0.013
			335.50	337.00	D003789	1.50	0.008		0.008
			337.00	338.50	D003790	1.50	<0.005		0.001
			338.50	340.00	D003791	1.50	0.005		0.005
			340.00	341.50	D003792	1.50	<0.005		0.001
			341.50	343.00	D003794	1.50	<0.005		0.001
			343.00	344.50	D003795	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	344.50	346.00	D003796	1.50	<0.005		0.001
	346.00	347.50	D003797	1.50	<0.005		0.001
	347.50	349.00	D003798	1.50	0.005		0.005
	349.00	350.50	D003799	1.50	0.005		0.005
	350.50	352.00	D003800	1.50	<0.005		0.001
	352.00	353.00	D003801	1.00	0.008		0.008
	353.00	354.20	D003802	1.20	<0.005		0.001
	354.20	355.50	D003804	1.30	<0.005		0.001
	355.50	357.00	D003805	1.50	<0.005		0.001
	357.00	358.50	D003806	1.50	<0.005		0.001
	358.50	360.00	D003807	1.50	<0.005		0.001
	360.00	361.50	D003808	1.50	<0.005		0.001
	361.50	363.00	D003809	1.50	<0.005		0.001
	363.00	364.50	D003811	1.50	<0.005		0.001
	364.50	366.00	D003812	1.50	0.021		0.021
	366.00	367.50	D003814	1.50	<0.005		0.001
	367.50	369.00	D003815	1.50	<0.005		0.001
	369.00	370.50	D003816	1.50	0.010		0.010
	370.50	372.00	D003817	1.50	0.005		0.005
	372.00	373.50	D003818	1.50	0.371		0.371
	373.50	375.00	D003819	1.50	<0.005		0.001
	375.00	376.50	D003820	1.50	<0.005		0.001
	376.50	378.00	D003821	1.50	0.005		0.005
	378.00	379.50	D003822	1.50	0.005		0.005
	379.50	381.00	D003824	1.50	<0.005		0.001
	381.00	382.50	D003825	1.50	<0.005		0.001
	382.50	384.00	D003826	1.50	0.016		0.016
	384.00	385.50	D003827	1.50	0.049		0.049
	385.50	387.00	D003828	1.50	0.035		0.035
	387.00	388.60	D003829	1.60	0.014		0.014
	388.60	390.00	D003830	1.40	0.010		0.010
	390.00	391.50	D003831	1.50	0.014		0.014
	391.50	393.00	D003832	1.50	0.030		0.030

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	393.00	394.10	D003834	1.10	0.023		0.023	
	394.10	395.50	D003835	1.40	0.285		0.285	
	395.50	397.00	D003836	1.50	0.018		0.018	
	397.00	398.50	D003837	1.50	0.005		0.005	
	398.50	400.00	D003838	1.50	0.089		0.089	
	400.00	401.50	D003839	1.50	0.018		0.018	
	401.50	403.00	D003840	1.50	<0.005		0.001	
	403.00	404.50	D003841	1.50	<0.005		0.001	
	404.50	406.00	D003842	1.50	0.028		0.028	
	406.00	407.50	D003844	1.50	<0.005		0.001	
	407.50	409.00	D003845	1.50	<0.005		0.001	
	409.00	410.50	D003846	1.50	<0.005		0.001	
	410.50	412.00	D003847	1.50	<0.005		0.001	
	412.00	413.50	D003848	1.50	<0.005		0.001	
	413.50	415.00	D003849	1.50	<0.005		0.001	
	415.00	416.50	D003851	1.50	0.005		0.005	
	416.50	418.00	D003852	1.50	0.009		0.009	
	418.00	419.50	D003854	1.50	0.015		0.015	
	419.50	421.00	D003855	1.50	<0.005		0.001	
	421.00	422.00	D003856	1.00	0.009		0.009	
	422.00	423.00	D003857	1.00	<0.005		0.001	
423.00	425.00	POR	423.00	424.00	D003858	1.00	<0.005	0.001
		<b>Porphyrique</b>	424.00	425.00	D003859	1.00	0.005	0.005
		phénocristaux automorphe 0.1-2 cm HM+	425.00	426.50	D003860	1.50	<0.005	0.001
			426.50	428.00	D003861	1.50	<0.005	0.001
			428.00	429.50	D003862	1.50	0.047	0.047
			429.50	431.00	D003864	1.50	0.005	0.005
			431.00	432.50	D003865	1.50	<0.005	0.001
			432.50	434.00	D003866	1.50	0.008	0.008
			434.00	435.50	D003867	1.50	<0.005	0.001
			435.50	437.00	D003868	1.50	0.007	0.007
			437.00	438.50	D003869	1.50	<0.005	0.001
			438.50	440.00	D003870	1.50	0.022	0.022

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			440.00	441.50	D003871	1.50		0.014	
			441.50	443.00	D003872	1.50		0.166	
			443.00	444.50	D003874	1.50		0.930	
			444.50	446.00	D003875	1.50		0.585	
			446.00	447.50	D003876	1.50		0.005	
			447.50	448.70	D003877	1.20		<0.005	
448.70	449.00	NR							
		<b>Carotte perdue</b>							
449.00	464.00	SY; MAS; FIN	449.00	450.50	D003878	1.50		0.005	0.005
		<b>Syénite; Roche massive; Grains fins</b>	450.50	452.00	D003879	1.50		0.030	0.030
		localement sub bréchique, qlq phénocristaux automorphe sub arrondi	452.00	453.50	D003880	1.50		<0.005	0.001
		HM++, ++calcite, SR++, PY fine diss	453.50	455.00	D003881	1.50		0.007	0.007
			455.00	456.50	D003882	1.50		<0.005	0.001
			456.50	458.00	D003884	1.50		<0.005	0.001
			458.00	459.50	D003885	1.50		0.005	0.005
			459.50	461.00	D003886	1.50		0.006	0.006
			461.00	462.50	D003887	1.50		0.006	0.006
			462.50	464.00	D003888	1.50		0.012	0.012
464.00		Fin du sondage							
		Nombre d'échantillons : 312							
		Nombre d'échantillons QAQC : 43							
		Longueur totale échantillonnée : 461.70							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	15.50	D003543	D003542	1.50	0.005	0.005
27.50	27.50	D003553	A3	0.00	0.621	0.621
41.00	42.50	D003563	D003562	1.50	0.086	0.086
50.00	50.00	D003570	M1	0.00	<0.005	0.001
53.00	53.00	D003573	B4	0.00	2.540	2.540
66.50	68.00	D003583	D003582	1.50	0.013	0.013
80.00	80.00	D003593	C4	0.00	1.345	1.345
93.50	95.00	D003603	D003602	1.50	0.058	0.058
101.90	101.90	D003610	M1	0.00	<0.005	0.001
104.00	104.00	D003613	D2	0.00	0.864	0.864
117.50	119.00	D003623	D003622	1.50	0.289	0.289
131.00	131.00	D003633	F2	0.00	8.070	8.070
144.50	146.00	D003643	D003642	1.50	0.188	0.188
153.50	153.50	D003650	M1	0.00	<0.005	0.001
156.50	156.50	D003653	G2	0.00	4.140	4.140
170.00	171.50	D003663	D003662	1.50	0.135	0.135
183.50	183.50	D003673	H	0.00	0.913	0.913
197.00	198.50	D003683	D003682	1.50	0.281	0.281
206.00	206.00	D003690	M1	0.00	0.005	0.005
209.00	209.00	D003693	A3	0.00	0.603	0.603
222.50	224.00	D003703	D003702	1.50	0.006	0.006
235.00	235.00	D003713	B4	0.00	2.550	2.550
248.50	250.00	D003723	D003722	1.50	0.012	0.012
257.50	257.50	D003730	M1	0.00	0.005	0.005
260.50	260.50	D003733	C4	0.00	1.345	1.345
274.00	275.50	D003743	D003742	1.50	0.017	0.017
287.50	287.50	D003753	D2	0.00	0.877	0.877
301.00	302.50	D003763	D003762	1.50	0.044	0.044
310.00	310.00	D003770	M1	0.00	0.006	0.006
313.00	313.00	D003773	G2	0.00	3.870	3.870
326.50	328.00	D003783	D003782	1.50	<0.005	0.001
340.00	340.00	D003793	F2	0.00	7.960	7.960
353.00	354.20	D003803	D003802	1.20	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
361.50	361.50	D003810	M1	0.00	<0.005	0.001
364.50	364.50	D003813	H	0.00	3.920	3.920
378.00	379.50	D003823	D003822	1.50	<0.005	0.001
391.50	391.50	D003833	A3	0.00	0.484	0.484
404.50	406.00	D003843	D003842	1.50	0.032	0.032
413.50	413.50	D003850	M1	0.00	<0.005	0.001
416.50	416.50	D003853	B4	0.00	2.580	2.580
428.00	429.50	D003863	D003862	1.50	0.055	0.055
441.50	441.50	D003873	C4	0.00	1.370	1.370
455.00	456.50	D003883	D003882	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-161**

Titre minier :

Section :                      631000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-18

Date de description :

Au :                      2010-04-25

Collet

UTM

Azimut :                0.00°

Plongée :              -68.00°

Longueur :            464.00 m

Est                      630 999.8

Nord                    5 374 200.1

Élévation              304.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	359.40°	-68.10°	Non
Reflex	8.00	359.40°	-68.10°	Non
Reflex	11.00	359.40°	-68.10°	Non
Reflex	14.00	0.00°	-68.70°	Non
Reflex	17.00	1.20°	-67.90°	Non
Reflex	20.00	0.30°	-67.40°	Non
Reflex	23.00	0.00°	-67.30°	Non
Reflex	26.00	359.90°	-67.10°	Non
Reflex	29.00	359.40°	-66.90°	Non
Reflex	32.00	359.70°	-67.10°	Non
Reflex	35.00	359.90°	-67.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.90°	-66.90°	Non
Reflex	41.00	359.90°	-66.90°	Non
Reflex	44.00	0.10°	-66.80°	Non
Reflex	47.00	359.90°	-66.60°	Non
Reflex	50.00	359.80°	-66.50°	Non
Reflex	53.00	359.60°	-66.30°	Non
Reflex	56.00	359.30°	-66.10°	Non
Reflex	59.00	359.00°	-66.00°	Non
Reflex	62.00	358.90°	-65.70°	Non
Reflex	65.00	358.90°	-65.40°	Non
Reflex	68.00	358.40°	-65.20°	Non
Reflex	71.00	358.60°	-64.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.10°	-64.70°	Non	Reflex	173.00	2.10°	-62.30°	Non
Reflex	77.00	359.70°	-64.60°	Non	Reflex	176.00	3.10°	-62.40°	Non
Reflex	80.00	0.50°	-64.60°	Non	Reflex	179.00	3.00°	-62.40°	Non
Reflex	83.00	0.80°	-64.40°	Non	Reflex	182.00	3.40°	-62.40°	Non
Reflex	86.00	0.50°	-64.20°	Non	Reflex	185.00	3.30°	-62.40°	Non
Reflex	89.00	0.60°	-64.00°	Non	Reflex	188.00	4.00°	-62.40°	Non
Reflex	92.00	0.50°	-63.90°	Non	Reflex	191.00	4.90°	-62.40°	Non
Reflex	95.00	0.20°	-63.80°	Non	Reflex	194.00	4.50°	-62.40°	Non
Reflex	98.00	0.10°	-63.40°	Non	Reflex	197.00	4.20°	-62.50°	Non
Reflex	101.00	0.70°	-63.50°	Non	Reflex	200.00	4.80°	-62.60°	Non
Reflex	104.00	0.90°	-63.50°	Non	Reflex	203.00	3.90°	-62.60°	Non
Reflex	107.00	0.80°	-63.50°	Non	Reflex	206.00	4.90°	-62.70°	Non
Reflex	110.00	0.80°	-63.50°	Non	Reflex	209.00	4.50°	-62.70°	Non
Reflex	113.00	0.50°	-63.30°	Non	Reflex	212.00	5.00°	-62.70°	Non
Reflex	116.00	359.90°	-62.90°	Non	Reflex	215.00	4.80°	-62.80°	Non
Reflex	119.00	359.90°	-62.70°	Non	Reflex	218.00	4.80°	-62.70°	Non
Reflex	122.00	359.90°	-62.70°	Non	Reflex	221.00	4.50°	-62.70°	Non
Reflex	125.00	0.30°	-62.50°	Non	Reflex	224.00	4.10°	-62.60°	Non
Reflex	128.00	0.50°	-62.40°	Non	Reflex	227.00	4.10°	-62.50°	Non
Reflex	131.00	1.20°	-62.70°	Non	Reflex	230.00	4.00°	-62.50°	Non
Reflex	134.00	1.60°	-62.80°	Non	Reflex	233.00	3.80°	-62.40°	Non
Reflex	137.00	1.90°	-62.80°	Non	Reflex	236.00	3.90°	-62.40°	Non
Reflex	140.00	1.90°	-62.70°	Non	Reflex	239.00	3.80°	-62.40°	Non
Reflex	143.00	2.20°	-62.70°	Non	Reflex	242.00	3.90°	-62.40°	Non
Reflex	146.00	2.30°	-62.80°	Non	Reflex	245.00	4.00°	-62.40°	Non
Reflex	149.00	2.50°	-62.80°	Non	Reflex	248.00	4.20°	-62.50°	Non
Reflex	152.00	2.50°	-62.70°	Non	Reflex	251.00	4.10°	-62.40°	Non
Reflex	155.00	2.20°	-62.50°	Non	Reflex	254.00	4.60°	-62.50°	Non
Reflex	158.00	1.30°	-62.50°	Non	Reflex	257.00	4.80°	-62.50°	Non
Reflex	161.00	1.90°	-62.30°	Non	Reflex	260.00	5.40°	-62.60°	Non
Reflex	164.00	2.60°	-62.30°	Non	Reflex	263.00	6.10°	-62.60°	Non
Reflex	167.00	1.90°	-62.20°	Non	Reflex	266.00	6.10°	-62.50°	Non
Reflex	170.00	2.30°	-62.20°	Non	Reflex	269.00	6.50°	-62.50°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	4.20°	-62.40°	Oui	Reflex	371.00	9.40°	-60.40°	Non
Reflex	275.00	6.30°	-62.40°	Non	Reflex	374.00	7.40°	-60.30°	Non
Reflex	278.00	5.60°	-62.30°	Non	Reflex	377.00	6.20°	-60.30°	Oui
Reflex	281.00	5.60°	-62.10°	Non	Reflex	380.00	7.80°	-60.30°	Non
Reflex	284.00	6.00°	-61.90°	Non	Reflex	383.00	7.90°	-60.30°	Non
Reflex	287.00	5.90°	-61.90°	Non	Reflex	386.00	9.00°	-60.20°	Non
Reflex	290.00	6.00°	-61.80°	Non	Reflex	389.00	9.50°	-60.30°	Non
Reflex	293.00	5.60°	-61.60°	Non	Reflex	392.00	8.70°	-60.20°	Non
Reflex	296.00	5.90°	-61.50°	Non	Reflex	395.00	12.40°	-60.20°	Non
Reflex	299.00	5.50°	-61.40°	Non	Reflex	398.00	11.40°	-60.20°	Non
Reflex	302.00	5.60°	-61.30°	Non	Reflex	401.00	11.80°	-60.20°	Non
Reflex	305.00	5.40°	-61.20°	Non	Reflex	404.00	10.90°	-60.20°	Non
Reflex	308.00	5.60°	-61.10°	Non	Reflex	407.00	8.20°	-60.20°	Non
Reflex	311.00	5.70°	-61.10°	Non	Reflex	410.00	9.10°	-60.20°	Non
Reflex	314.00	6.40°	-61.00°	Non	Reflex	413.00	11.50°	-60.20°	Non
Reflex	317.00	6.50°	-60.90°	Non	Reflex	416.00	11.90°	-60.20°	Non
Reflex	320.00	5.80°	-60.80°	Non	Reflex	419.00	12.80°	-60.20°	Non
Reflex	323.00	6.50°	-60.70°	Non	Reflex	422.00	12.10°	-60.20°	Non
Reflex	326.00	6.90°	-60.70°	Non	Reflex	425.00	12.40°	-60.20°	Non
Reflex	329.00	6.80°	-60.50°	Non	Reflex	428.00	13.00°	-60.20°	Non
Reflex	332.00	6.90°	-60.50°	Non	Reflex	431.00	13.10°	-60.30°	Non
Reflex	335.00	7.40°	-60.40°	Non	Reflex	434.00	13.70°	-60.30°	Non
Reflex	338.00	8.40°	-60.50°	Non	Reflex	437.00	12.50°	-60.30°	Non
Reflex	341.00	9.30°	-60.50°	Non	Reflex	440.00	12.70°	-60.20°	Non
Reflex	344.00	7.90°	-60.50°	Non	Reflex	443.00	13.00°	-60.20°	Non
Reflex	347.00	9.50°	-60.50°	Non	Reflex	446.00	13.40°	-60.20°	Non
Reflex	350.00	8.80°	-60.50°	Non	Reflex	449.00	13.50°	-60.20°	Non
Reflex	353.00	9.90°	-60.60°	Non	Reflex	452.00	13.80°	-60.10°	Non
Reflex	356.00	8.70°	-60.60°	Non	Reflex	455.00	14.20°	-60.10°	Non
Reflex	359.00	11.20°	-60.60°	Oui	Reflex	458.00	13.20°	-60.10°	Non
Reflex	362.00	9.70°	-60.50°	Non	Reflex	461.00	15.40°	-60.10°	Non
Reflex	365.00	7.90°	-60.50°	Non	Reflex	464.00	14.00°	-60.10°	Non
Reflex	368.00	9.80°	-60.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.60	MT						
		<b>Mort-terrain</b>						
3.60	10.50	SY; FIN	3.60	5.00	D008051	1.40	0.070	0.070
		<b>Syénite; Grains fins</b>	5.00	6.50	D008052	1.50	0.256	0.256
		Syénite à grains fins.	6.50	8.00	D008053	1.50	0.009	0.009
			8.00	9.00	D008054	1.00	0.008	0.008
			9.00	10.50	D008055	1.50	0.009	0.009
10.50	143.80	BA; FIN; AMY; COU	10.50	12.00	D008056	1.50	0.010	0.010
		<b>Basalte 45°; Grains fins; Amygdalaire; Cousiné</b>	12.00	13.50	D008058	1.50	0.005	0.005
		Basalte à grains fins avec passage de amygdalaire et rarement sporadique.	13.50	15.00	D008059	1.50	<0.005	0.001
			15.00	16.50	D008060	1.50	0.005	0.005
			16.50	18.00	D008061	1.50	<0.005	0.001
			18.00	19.50	D008062	1.50	<0.005	0.001
			19.50	21.00	D008063	1.50	<0.005	0.001
			21.00	22.50	D008064	1.50	0.006	0.006
			22.50	24.00	D008065	1.50	<0.005	0.001
			24.00	25.50	D008066	1.50	0.005	0.005
			25.50	27.00	D008068	1.50	<0.005	0.001
			27.00	28.50	D008069	1.50	0.006	0.006
			28.50	30.00	D008070	1.50	<0.005	0.001
			30.00	31.50	D008071	1.50	0.007	0.007
			31.50	33.00	D008072	1.50	0.032	0.032
			33.00	34.50	D008073	1.50	<0.005	0.001
			34.50	36.00	D008074	1.50	<0.005	0.001
			36.00	37.50	D008075	1.50	<0.005	0.001
			37.50	39.00	D008076	1.50	<0.005	0.001
			39.00	40.50	D008078	1.50	0.006	0.006
			40.50	42.00	D008079	1.50	0.006	0.006
			42.00	43.50	D008080	1.50	7.440	7.440
			43.50	45.00	D008081	1.50	0.021	0.021
			45.00	46.50	D008083	1.50	0.024	0.024
			46.50	48.00	D008084	1.50	<0.005	0.001
			48.00	49.50	D008085	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.50	51.00	D008086	1.50	<0.005		0.001
	51.00	52.50	D008088	1.50	<0.005		0.001
	52.50	54.00	D008089	1.50	0.005		0.005
	54.00	55.50	D008090	1.50	0.007		0.007
	55.50	57.00	D008091	1.50	<0.005		0.001
	57.00	58.50	D008092	1.50	<0.005		0.001
	58.50	60.00	D008093	1.50	<0.005		0.001
	60.00	61.50	D008094	1.50	0.005		0.005
	61.50	63.00	D008095	1.50	<0.005		0.001
	63.00	64.50	D008096	1.50	<0.005		0.001
	64.50	66.00	D008098	1.50	<0.005		0.001
	66.00	67.50	D008099	1.50	<0.005		0.001
	67.50	69.00	D008100	1.50	<0.005		0.001
	69.00	70.50	D008101	1.50	<0.005		0.001
	70.50	72.00	D008103	1.50	<0.005		0.001
	72.00	73.50	D008104	1.50	0.008		0.008
	73.50	75.00	D008105	1.50	<0.005		0.001
	75.00	76.50	D008106	1.50	0.006		0.006
	76.50	78.00	D008108	1.50	0.017		0.017
	78.00	79.50	D008109	1.50	0.014		0.014
	79.50	81.00	D008110	1.50	0.007		0.007
	81.00	82.50	D008111	1.50	0.006		0.006
	82.50	84.00	D008112	1.50	0.005		0.005
	84.00	85.50	D008113	1.50	<0.005		0.001
	85.50	87.00	D008114	1.50	0.008		0.008
	87.00	88.50	D008115	1.50	<0.005		0.001
	88.50	90.00	D008116	1.50	0.011		0.011
	90.00	91.50	D008118	1.50	0.015		0.015
	91.50	93.00	D008119	1.50	0.007		0.007
	93.00	94.50	D008120	1.50	<0.005		0.001
	94.50	96.00	D008121	1.50	0.006		0.006
	96.00	97.50	D008122	1.50	0.006		0.006
	97.50	99.00	D008123	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			99.00	100.50	D008124	1.50	<0.005		0.001
			100.50	102.00	D008125	1.50	<0.005		0.001
			102.00	103.50	D008126	1.50	<0.005		0.001
			103.50	105.00	D008128	1.50	<0.005		0.001
			105.00	106.50	D008129	1.50	<0.005		0.001
			106.50	108.00	D008130	1.50	<0.005		0.001
			108.00	109.50	D008131	1.50	<0.005		0.001
			109.50	111.00	D008132	1.50	<0.005		0.001
			111.00	112.50	D008133	1.50	<0.005		0.001
			112.50	114.00	D008134	1.50	<0.005		0.001
			114.00	115.50	D008135	1.50	<0.005		0.001
			115.50	117.00	D008136	1.50	<0.005		0.001
			117.00	118.50	D008138	1.50	0.005		0.005
			118.50	120.00	D008139	1.50	0.011		0.011
			120.00	121.50	D008140	1.50	<0.005		0.001
			121.50	123.00	D008141	1.50	<0.005		0.001
			123.00	124.50	D008143	1.50	<0.005		0.001
			124.50	126.00	D008144	1.50	<0.005		0.001
			126.00	127.50	D008145	1.50	0.009		0.009
			127.50	129.00	D008146	1.50	<0.005		0.001
			129.00	130.50	D008148	1.50	<0.005		0.001
			130.50	132.00	D008149	1.50	0.034		0.034
			132.00	133.50	D008150	1.50	<0.005		0.001
			133.50	135.00	D008151	1.50	<0.005		0.001
			135.00	136.50	D008152	1.50	<0.005		0.001
			136.50	138.00	D008153	1.50	<0.005		0.001
			138.00	139.50	D008154	1.50	<0.005		0.001
			139.50	141.00	D008155	1.50	0.006		0.006
			141.00	142.50	D008156	1.50	0.007		0.007
			142.50	143.80	D008158	1.30	0.008		0.008
143.80	254.30	SY; POR; FIN; MTY	143.80	145.50	D008159	1.70	0.014		0.014
		<b>Syénite 55*; Porphyrique; Grains fins; Grains moyens</b>	145.50	147.00	D008160	1.50	2.000		2.000
		Syénite, à grains fins à grains moyens, porphyrique avec de	147.00	148.50	D008161	1.50	0.050		0.050
		phénocristaux Xmm à Xcm.							

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.50	150.00	D008162	1.50	0.162		0.162
	150.00	151.50	D008163	1.50	0.523		0.523
	151.50	153.00	D008164	1.50	0.005		0.005
	153.00	154.50	D008165	1.50	0.010		0.010
	154.50	156.00	D008166	1.50	0.050		0.050
	156.00	157.50	D008168	1.50	0.048		0.048
	157.50	159.00	D008169	1.50	0.022		0.022
	159.00	160.50	D008170	1.50	0.013		0.013
	160.50	162.00	D008171	1.50	0.023		0.023
	162.00	163.50	D008172	1.50	0.019		0.019
	163.50	165.00	D008173	1.50	0.015		0.015
	165.00	166.50	D008174	1.50	0.022		0.022
	166.50	168.00	D008175	1.50	0.012		0.012
	168.00	169.50	D008176	1.50	0.009		0.009
	169.50	171.00	D008178	1.50	0.283		0.283
	171.00	172.50	D008179	1.50	1.480		1.480
	172.50	174.00	D008180	1.50	0.013		0.013
	174.00	175.50	D008181	1.50	0.030		0.030
	175.50	177.00	D008183	1.50	0.068		0.068
	177.00	178.50	D008184	1.50	0.130		0.130
	178.50	180.00	D008185	1.50	0.132		0.132
	180.00	181.50	D008186	1.50	0.094		0.094
	181.50	183.00	D008188	1.50	0.038		0.038
	183.00	184.50	D008189	1.50	0.083		0.083
	184.50	186.00	D008190	1.50	0.025		0.025
	186.00	187.50	D008191	1.50	0.073		0.073
	187.50	189.00	D008192	1.50	0.012		0.012
	189.00	190.50	D008193	1.50	0.008		0.008
	190.50	192.00	D008194	1.50	0.011		0.011
	192.00	193.50	D008195	1.50	0.014		0.014
	193.50	195.00	D008196	1.50	0.046		0.046
	195.00	196.50	D008198	1.50	0.013		0.013
	196.50	198.00	D008199	1.50	0.013		0.013

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	198.00	199.50	D008200	1.50	0.010		0.010
	199.50	201.00	D008201	1.50	0.118		0.118
	201.00	202.50	D008202	1.50	0.035		0.035
	202.50	204.00	D008203	1.50	0.016		0.016
	204.00	205.50	D008204	1.50	0.033		0.033
	205.50	207.00	D008205	1.50	0.009		0.009
	207.00	208.50	D008206	1.50	0.134		0.134
	208.50	210.00	D008208	1.50	0.025		0.025
	210.00	211.50	D008209	1.50	0.096		0.096
	211.50	213.00	D008210	1.50	0.169		0.169
	213.00	214.50	D008211	1.50	0.015		0.015
	214.50	216.00	D008212	1.50	0.019		0.019
	216.00	217.50	D008213	1.50	0.034		0.034
	217.50	219.00	D008214	1.50	0.014		0.014
	219.00	220.50	D008215	1.50	0.064		0.064
	220.50	222.00	D008216	1.50	0.022		0.022
	222.00	223.50	D008218	1.50	<0.005		0.001
	223.50	225.00	D008219	1.50	0.006		0.006
	225.00	226.50	D008220	1.50	<0.005		0.001
	226.50	228.00	D008221	1.50	<0.005		0.001
	228.00	229.50	D008223	1.50	<0.005		0.001
	229.50	231.00	D008224	1.50	<0.005		0.001
	231.00	232.50	D008225	1.50	0.007		0.007
	232.50	234.00	D008226	1.50	0.010		0.010
	234.00	235.50	D008228	1.50	0.007		0.007
	235.50	237.00	D008229	1.50	<0.005		0.001
	237.00	238.50	D008230	1.50	<0.005		0.001
	238.50	240.00	D008231	1.50	<0.005		0.001
	240.00	241.50	D008232	1.50	0.027		0.027
	241.50	243.00	D008233	1.50	<0.005		0.001
	243.00	244.50	D008234	1.50	0.005		0.005
	244.50	246.00	D008235	1.50	0.062		0.062
	246.00	247.50	D008236	1.50	0.142		0.142

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
254.30	322.30	BA; FIN; AMY; COU <b>Basalte 45°; Grains fins; Amygdalaire; Cousiné</b> Basalte à grains fins avec de passage amygdalaire et coussiné.	247.50	249.00	D008238	1.50	0.024		0.024
			249.00	250.50	D008239	1.50	0.007		0.007
			250.50	252.00	D008240	1.50	0.015		0.015
			252.00	253.00	D008241	1.00	0.005		0.005
			253.00	254.30	D008242	1.30	0.053		0.053
			254.30	256.00	D008243	1.70	<0.005		0.001
			256.00	257.50	D008244	1.50	<0.005		0.001
			257.50	259.00	D008245	1.50	<0.005		0.001
			259.00	260.50	D008246	1.50	0.127		0.127
			260.50	262.00	D008248	1.50	0.510		0.510
			262.00	263.50	D008249	1.50	0.252		0.252
			263.50	265.00	D008250	1.50	0.005		0.005
			265.00	266.50	D008251	1.50	<0.005		0.001
			266.50	268.00	D008252	1.50	0.263		0.263
			268.00	269.50	D008253	1.50	2.980		2.980
			269.50	271.00	D008254	1.50	0.007		0.007
			271.00	272.50	D008255	1.50	0.126		0.126
			272.50	274.00	D008256	1.50	0.234		0.234
			274.00	275.50	D008258	1.50	0.009		0.009
			275.50	277.00	D008259	1.50	0.328		0.328
			277.00	278.50	D008260	1.50	0.009		0.009
			278.50	280.00	D008261	1.50	<0.005		0.001
			280.00	281.50	D008263	1.50	<0.005		0.001
			281.50	283.00	D008264	1.50	<0.005		0.001
			283.00	284.50	D008265	1.50	0.005		0.005
			284.50	286.00	D008266	1.50	0.039		0.039
			286.00	287.50	D008268	1.50	0.167		0.167
			287.50	289.00	D008269	1.50	0.008		0.008
			289.00	290.50	D008270	1.50	<0.005		0.001
			290.50	292.00	D008271	1.50	<0.005		0.001
292.00	293.50	D008272	1.50	0.005		0.005			
293.50	295.00	D008273	1.50	0.005		0.005			
295.00	296.50	D008274	1.50	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
322.30	464.00	SY; FIN; MTY; POR <b>Syénite 5"; Grains fins; Grains moyens; Porphyrique</b> Syénite, à grains fis à moyens, porphyrique à phénocristaux Xmm à Xcm.	296.50	298.00	D008275	1.50	0.482		0.482
			298.00	299.50	D008276	1.50	0.092		0.092
			299.50	301.00	D008278	1.50	0.011		0.011
			301.00	302.50	D008279	1.50	0.386		0.386
			302.50	304.00	D008280	1.50	1.860		1.860
			304.00	305.50	D008281	1.50	0.010		0.010
			305.50	307.00	D008282	1.50	0.022		0.022
			307.00	308.50	D008283	1.50	0.006		0.006
			308.50	310.00	D008284	1.50	1.025		1.025
			310.00	311.50	D008285	1.50	0.556		0.556
			311.50	313.00	D008286	1.50	0.007		0.007
			313.00	314.50	D008288	1.50	0.027		0.027
			314.50	316.00	D008289	1.50	0.563		0.563
			316.00	317.50	D008290	1.50	0.026		0.026
			317.50	319.00	D008291	1.50	1.615		1.615
			319.00	320.70	D008292	1.70	4.300		4.300
			320.70	322.30	D008293	1.60	2.500		2.500
			322.30	324.00	D008294	1.70	0.138		0.138
			324.00	325.50	D008295	1.50	0.008		0.008
			325.50	327.00	D008296	1.50	0.008		0.008
			327.00	328.50	D008298	1.50	0.065		0.065
			328.50	330.00	D008299	1.50	<0.005		0.001
			330.00	331.50	D008300	1.50	0.015		0.015
			331.50	333.00	D008301	1.50	<0.005		0.001
			333.00	334.50	D008303	1.50	<0.005		0.001
			334.50	336.00	D008304	1.50	0.017		0.017
			336.00	337.50	D008305	1.50	0.011		0.011
			337.50	339.00	D008306	1.50	0.015		0.015
339.00	340.50	D008308	1.50	<0.005		0.001			
340.50	342.00	D008309	1.50	0.010		0.010			
342.00	343.50	D008310	1.50	<0.005		0.001			
343.50	345.00	D008311	1.50	0.030		0.030			
345.00	346.50	D008312	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	346.50	348.00	D008313	1.50	0.006		0.006
	348.00	349.50	D008314	1.50	<0.005		0.001
	349.50	351.00	D008315	1.50	<0.005		0.001
	351.00	352.50	D008316	1.50	<0.005		0.001
	352.50	354.00	D008318	1.50	<0.005		0.001
	354.00	355.50	D008319	1.50	<0.005		0.001
	355.50	357.00	D008320	1.50	0.005		0.005
	357.00	358.50	D008321	1.50	<0.005		0.001
	358.50	360.00	D008322	1.50	<0.005		0.001
	360.00	361.50	D008323	1.50	<0.005		0.001
	361.50	363.00	D008324	1.50	<0.005		0.001
	363.00	364.50	D008325	1.50	<0.005		0.001
	364.50	366.00	D008326	1.50	<0.005		0.001
	366.00	367.50	D008328	1.50	0.005		0.005
	367.50	369.00	D008329	1.50	0.007		0.007
	369.00	370.50	D008330	1.50	0.005		0.005
	370.50	372.00	D008331	1.50	0.097		0.097
	372.00	373.50	D008332	1.50	<0.005		0.001
	373.50	375.00	D008333	1.50	0.005		0.005
	375.00	376.50	D008334	1.50	<0.005		0.001
	376.50	378.00	D008335	1.50	0.055		0.055
	378.00	379.50	D008336	1.50	0.381		0.381
	379.50	381.00	D008338	1.50	0.227		0.227
	381.00	382.50	D008339	1.50	0.246		0.246
	382.50	384.00	D008340	1.50	0.785		0.785
	384.00	385.50	D008341	1.50	0.076		0.076
	385.50	387.00	D008343	1.50	0.025		0.025
	387.00	388.50	D008344	1.50	0.014		0.014
	388.50	390.00	D008345	1.50	<0.005		0.001
	390.00	391.50	D008346	1.50	<0.005		0.001
	391.50	393.00	D008348	1.50	<0.005		0.001
	393.00	394.50	D008349	1.50	<0.005		0.001
	394.50	396.00	D008350	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	396.00	397.50	D008351	1.50	<0.005		0.001
	397.50	399.00	D008352	1.50	<0.005		0.001
	399.00	400.50	D008353	1.50	<0.005		0.001
	400.50	402.00	D008354	1.50	0.008		0.008
	402.00	403.50	D008355	1.50	0.023		0.023
	403.50	405.00	D008356	1.50	0.032		0.032
	405.00	406.50	D008358	1.50	0.024		0.024
	406.50	408.00	D008359	1.50	<0.005		0.001
	408.00	409.50	D008360	1.50	<0.005		0.001
	409.50	411.00	D008361	1.50	0.006		0.006
	411.00	412.50	D008362	1.50	<0.005		0.001
	412.50	414.00	D008363	1.50	<0.005		0.001
	414.00	415.50	D008364	1.50	<0.005		0.001
	415.50	417.00	D008365	1.50	0.020		0.020
	417.00	418.50	D008366	1.50	0.091		0.091
	418.50	420.00	D008368	1.50	0.024		0.024
	420.00	421.50	D008369	1.50	0.026		0.026
	421.50	423.00	D008370	1.50	0.012		0.012
	423.00	424.50	D008371	1.50	0.008		0.008
	424.50	426.00	D008372	1.50	0.071		0.071
	426.00	427.50	D008373	1.50	0.019		0.019
	427.50	429.00	D008374	1.50	<0.005		0.001
	429.00	430.50	D008375	1.50	<0.005		0.001
	430.50	432.00	D008376	1.50	<0.005		0.001
	432.00	433.50	D008378	1.50	<0.005		0.001
	433.50	435.00	D008379	1.50	<0.005		0.001
	435.00	436.50	D008380	1.50	0.191		0.191
	436.50	438.00	D008381	1.50	0.328		0.328
	438.00	439.50	D008383	1.50	<0.005		0.001
	439.50	441.00	D008384	1.50	<0.005		0.001
	441.00	442.50	D008385	1.50	<0.005		0.001
	442.50	444.00	D008386	1.50	<0.005		0.001
	444.00	445.50	D008388	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	445.50	447.00	D008389	1.50	0.016		0.016
	447.00	448.50	D008390	1.50	0.117		0.117
	448.50	450.00	D008391	1.50	0.027		0.027
	450.00	451.50	D008392	1.50	<0.005		0.001
	451.50	453.00	D008393	1.50	<0.005		0.001
	453.00	454.50	D008394	1.50	<0.005		0.001
	454.50	456.00	D008395	1.50	<0.005		0.001
	456.00	457.50	D008396	1.50	<0.005		0.001
	457.50	459.00	D008398	1.50	<0.005		0.001
	459.00	460.50	D008399	1.50	<0.005		0.001
	460.50	462.00	D008400	1.50	0.006		0.006
	462.00	463.00	D008401	1.00	0.020		0.020
	463.00	464.00	D008402	1.00	0.008		0.008
464.00	Fin du sondage Nombre d'échantillons : 308 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 460.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
10.50	12.50	D008057	D008056	2.00	0.010	0.010
24.00	25.50	D008067	G2	1.50	3.590	3.590
37.50	39.00	D008077	D008076	1.50	<0.005	0.001
43.50	45.00	D008082	M1	1.50	<0.005	0.001
49.50	51.00	D008087	H	1.50	0.955	0.955
63.00	64.50	D008097	D008096	1.50	<0.005	0.001
69.00	70.50	D008102	M1	1.50	<0.005	0.001
75.00	76.50	D008107	A3	1.50	0.564	0.564
88.50	90.00	D008117	D008116	1.50	<0.005	0.001
102.00	103.50	D008127	H	1.50	0.780	0.780
115.50	117.00	D008137	D008136	1.50	<0.005	0.001
121.50	123.00	D008142	M1	1.50	<0.005	0.001
127.50	129.00	D008147	D2	1.50	0.825	0.825
141.00	142.50	D008157	D008156	1.50	0.009	0.009
154.50	156.00	D008167	B4	1.50	2.590	2.590
168.00	169.50	D008177	D008176	1.50	0.008	0.008
174.00	175.50	D008182	M1	1.50	<0.005	0.001
180.00	181.50	D008187	F2	1.50	6.380	6.380
193.50	195.00	D008197	D008196	1.50	0.096	0.096
207.00	207.00	D008207	H	0.00	1.005	1.005
220.50	222.00	D008217	D008216	1.50	0.021	0.021
226.50	228.00	D008222	M1	1.50	<0.005	0.001
232.50	234.00	D008227	D2	1.50	0.849	0.849
246.00	247.50	D008237	D008236	1.50	0.160	0.160
259.00	260.50	D008247	A3	1.50	0.605	0.605
272.50	274.00	D008257	D008256	1.50	0.264	0.264
278.50	280.00	D008262	M1	1.50	<0.005	0.001
284.50	286.00	D008267	G2	1.50	4.020	4.020
298.00	299.50	D008277	D008276	1.50	0.097	0.097
311.50	313.00	D008287	C4	1.50	1.330	1.330
325.50	327.00	D008297	D008296	1.50	0.010	0.010
331.50	333.00	D008302	M1	1.50	<0.005	0.001
337.50	339.00	D008307	D2	1.50	0.910	0.910

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
351.00	352.50	D008317	D008316	1.50	<0.005	0.001
364.50	366.00	D008327	F2	1.50	8.450	8.450
378.00	379.50	D008337	D008336	1.50	0.380	0.380
384.00	385.50	D008342	M1	1.50	<0.005	0.001
390.00	391.50	D008347	G2	1.50	4.040	4.040
403.50	405.00	D008357	D008356	1.50	0.031	0.031
417.00	418.50	D008367	H	1.50	1.050	1.050
430.50	432.00	D008377	D008376	1.50	<0.005	0.001
436.50	438.00	D008382	M1	1.50	<0.005	0.001
442.50	444.00	D008387	A3	1.50	0.614	0.614
456.00	457.50	D008397	D008396	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	355.80°	-51.80°	Non
Reflex	77.00	358.20°	-51.70°	Non
Reflex	80.00	358.60°	-51.80°	Non
Reflex	83.00	358.90°	-51.70°	Non
Reflex	86.00	359.40°	-51.80°	Non
Reflex	89.00	0.00°	-51.70°	Non
Reflex	92.00	359.30°	-51.60°	Non
Reflex	95.00	358.90°	-51.50°	Non
Reflex	98.00	0.40°	-51.40°	Non
Reflex	101.00	357.90°	-50.10°	Non
Reflex	104.00	359.40°	-51.20°	Non
Reflex	107.00	356.60°	-51.10°	Non
Reflex	110.00	358.30°	-51.00°	Non
Reflex	113.00	358.10°	-51.00°	Non
Reflex	116.00	0.10°	-50.80°	Non
Reflex	119.00	0.70°	-50.70°	Non
Reflex	122.00	1.20°	-50.60°	Non
Reflex	125.00	1.60°	-50.50°	Non
Reflex	128.00	1.50°	-50.40°	Non
Reflex	131.00	0.50°	-49.20°	Non
Reflex	134.00	1.30°	-50.20°	Non
Reflex	137.00	1.20°	-50.10°	Non
Reflex	140.00	1.00°	-49.70°	Non
Reflex	143.00	0.90°	-49.80°	Non
Reflex	146.00	1.00°	-49.70°	Non
Reflex	149.00	0.90°	-49.60°	Non
Reflex	152.00	1.00°	-49.50°	Non
Reflex	155.00	1.00°	-49.40°	Non
Reflex	158.00	0.80°	-49.30°	Non
Reflex	161.00	0.40°	-49.60°	Non
Reflex	164.00	1.70°	-48.90°	Non
Reflex	167.00	0.50°	-49.10°	Non
Reflex	170.00	0.70°	-49.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	0.70°	-49.20°	Non
Reflex	176.00	0.70°	-49.20°	Non
Reflex	179.00	0.70°	-49.10°	Non
Reflex	182.00	0.80°	-49.10°	Non
Reflex	185.00	0.50°	-49.10°	Non
Reflex	188.00	0.60°	-49.10°	Non
Reflex	191.00	0.50°	-49.10°	Non
Reflex	194.00	0.60°	-49.10°	Non
Reflex	197.00	0.50°	-49.10°	Non
Reflex	200.00	0.60°	-49.10°	Non
Reflex	203.00	0.80°	-49.10°	Non
Reflex	206.00	0.60°	-49.10°	Non
Reflex	209.00	0.90°	-49.00°	Non
Reflex	212.00	1.00°	-49.10°	Non
Reflex	215.00	0.70°	-48.80°	Non
Reflex	218.00	0.70°	-48.80°	Non
Reflex	221.00	0.30°	-48.80°	Non
Reflex	224.00	0.90°	-48.60°	Non
Reflex	227.00	0.40°	-48.60°	Non
Reflex	230.00	0.30°	-48.60°	Non
Reflex	233.00	0.30°	-48.70°	Non
Reflex	236.00	1.10°	-48.90°	Non
Reflex	239.00	1.00°	-48.80°	Non
Reflex	242.00	1.20°	-48.70°	Non
Reflex	245.00	1.20°	-48.70°	Non
Reflex	248.00	0.80°	-48.60°	Non
Reflex	251.00	0.70°	-48.60°	Non
Reflex	254.00	0.50°	-48.60°	Non
Reflex	257.00	0.30°	-48.50°	Non
Reflex	260.00	0.40°	-48.50°	Non
Reflex	263.00	0.30°	-48.40°	Non
Reflex	266.00	0.40°	-48.40°	Non
Reflex	269.00	0.40°	-48.30°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	0.60°	-48.50°	Non					
Reflex	275.00	0.50°	-48.40°	Non					
Reflex	278.00	0.60°	-48.50°	Non					
Reflex	281.00	359.90°	-46.40°	Non					
Reflex	284.00	357.00°	-42.80°	Non					
Reflex	287.00	0.80°	-48.40°	Non					
Reflex	290.00	0.70°	-48.40°	Non					
Reflex	293.00	0.70°	-48.40°	Non					
Reflex	296.00	0.80°	-48.30°	Non					
Reflex	299.00	0.90°	-48.30°	Non					
Reflex	302.00	0.60°	-48.40°	Non					
Reflex	305.00	0.70°	-48.40°	Non					
Reflex	308.00	0.60°	-48.30°	Non					
Reflex	311.00	0.70°	-48.30°	Non					
Reflex	314.00	0.70°	-48.20°	Non					
Reflex	317.00	0.80°	-48.30°	Non					
Reflex	320.00	0.70°	-48.30°	Non					
Reflex	323.00	0.60°	-48.30°	Non					
Reflex	326.00	0.80°	-48.30°	Non					
Reflex	329.00	0.90°	-48.30°	Non					
Reflex	331.70	0.80°	-48.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	33.00	MT <b>Mort-terrain</b>						
33.00	66.40	BA; MAS <b>Basalte; Roche massive</b> aphanitique, localement silicification et bréchification, laminations, intercalations de tuf graphiteux, SR++, CL++, calcite, PY fine diss	33.00	34.50	D002461	1.50	<0.005	0.001
			34.50	36.00	D002462	1.50	0.009	0.009
			36.00	37.50	D002463	1.50	0.008	0.008
			37.50	39.00	D002464	1.50	0.032	0.032
			39.00	40.50	D002465	1.50	0.007	0.007
			40.50	42.00	D002466	1.50	0.017	0.017
41.20	42.60	FRC <b>Fracturé</b> fragments mêlés cm abec localement boue de faille verdâtre	42.00	43.50	D002467	1.50	0.015	0.015
			43.50	45.00	D002468	1.50	<0.005	0.001
			45.00	46.50	D002469	1.50	0.007	0.007
			46.50	48.00	D002471	1.50	0.005	0.005
			48.00	49.00	D002472	1.00	0.006	0.006
49.00	50.10	QZVN <b>Veine de Quartz massive 40°</b> veine de QZ avec fragments d'éponte chloritisé, et séricitisé, BO+, graphite, PY fine	49.00	50.10	D002473	1.10	0.025	0.025
			50.10	51.50	D002474	1.40	0.046	0.046
			51.50	53.00	D002475	1.50	0.006	0.006
			53.00	54.50	D002476	1.50	0.063	0.063
			54.50	56.00	D002477	1.50	0.125	0.125
			56.00	57.50	D002478	1.50	0.022	0.022
			57.50	59.00	D002479	1.50	0.096	0.096
			59.00	60.50	D002481	1.50	0.030	0.030
			60.50	62.00	D002482	1.50	0.006	0.006
			62.00	63.50	D002483	1.50	<0.005	0.001
			63.50	65.00	D002484	1.50	0.011	0.011
			65.00	66.40	D002485	1.40	0.056	0.056
66.40	120.00	SY; MAS; POR <b>Syénite 40°; Roche massive; Porphyrique</b> grain fin, localement chloritisation ou hématitisation, calcite, oxydes de carbonâtes, passage bréchique à sub bréchique, PY fine diss	66.40	68.00	D002486	1.60	<0.005	0.001
			68.00	69.00	D002487	1.00	<0.005	0.001
			69.00	70.50	D002488	1.50	0.011	0.011
			70.50	72.00	D002489	1.50	0.009	0.009
			72.00	73.50	D002491	1.50	0.006	0.006
			73.50	75.00	D002492	1.50	<0.005	0.001
			75.00	76.50	D002493	1.50	0.018	0.018
			76.50	78.00	D002494	1.50	0.105	0.105

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			78.00	79.50	D002495	1.50	0.040		0.040
			79.50	80.50	D002496	1.00	0.027		0.027
			80.50	82.00	D002498	1.50	0.347		0.347
			82.00	83.50	D002499	1.50	0.005		0.005
			83.50	85.00	D002501	1.50	0.005		0.005
			85.00	86.50	D002502	1.50	0.031		0.031
			86.50	88.00	D002503	1.50	0.007		0.007
			88.00	89.50	D002504	1.50	0.084		0.084
66.40	75.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe à sub automorphe 0.5-2 cm, hématite, chlorite, biotite et PY fine							
89.50	95.00	SY; POR <b>Syénite; Porphyrique</b> grains fin phénocristaux de FP automorphe à sub automorphe, hématite et légère séricitisation altération en calcite	89.50	91.00	D002505	1.50	<0.005		0.001
			91.00	92.50	D002506	1.50	0.011		0.011
			92.50	94.00	D002507	1.50	0.017		0.017
			94.00	95.00	D002508	1.00	0.642		0.642
			95.00	96.50	D002509	1.50	0.008		0.008
			96.50	98.00	D002511	1.50	0.030		0.030
			98.00	99.50	D002512	1.50	0.048		0.048
99.50	108.50	SY; POR <b>Syénite; Porphyrique</b> grains fin phénocristaux automorphe ou sub arrondi ± 0.2-2 cm, hématite, chloritisation, SR++, altération en calcite, PY fine diss	99.50	101.00	D002513	1.50	0.013		0.013
			101.00	102.50	D002514	1.50	0.170		0.170
			102.50	104.00	D002515	1.50	0.089		0.089
			104.00	105.50	D002516	1.50	<0.005		0.001
			105.50	107.00	D002517	1.50	0.017		0.017
			107.00	108.50	D002518	1.50	0.010		0.010
			108.50	110.00	D002519	1.50	0.005		0.005
			110.00	111.50	D002521	1.50	0.006		0.006
			111.50	113.00	D002522	1.50	<0.005		0.001
			113.00	114.50	D002523	1.50	0.020		0.020
			114.50	116.00	D002524	1.50	0.007		0.007
116.00	117.50	D002525	1.50	0.008		0.008			
117.50	119.00	D002526	1.50	0.191		0.191			
119.00	120.00	D002527	1.00	0.022		0.022			
120.00	143.00	BA; MAS	120.00	121.50	D002528	1.50	0.119		0.119

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Basalte; Roche massive</b> microlitique, localement vacuoles et faible laminations sub // cisaillement ± 40° ac, légèrement blanchi, CL++, PY fine irrég diss	121.50	123.00	D002529	1.50	0.008		0.008
			123.00	124.50	D002531	1.50	0.008		0.008
			124.50	126.00	D002532	1.50	0.008		0.008
			126.00	127.50	D002533	1.50	0.006		0.006
			127.50	129.00	D002534	1.50	0.010		0.010
			129.00	130.50	D002535	1.50	0.014		0.014
			130.50	132.00	D002536	1.50	<0.005		0.001
			132.00	133.50	D002538	1.50	<0.005		0.001
			133.50	135.00	D002539	1.50	<0.005		0.001
			135.00	136.50	D002541	1.50	0.005		0.005
			136.50	138.00	D002542	1.50	<0.005		0.001
			138.00	139.50	D002543	1.50	0.005		0.005
			139.50	141.00	D002544	1.50	<0.005		0.001
			141.00	142.00	D002545	1.00	<0.005		0.001
			142.00	143.00	D002546	1.00	0.005		0.005
143.00	144.50	D002547	1.50	0.005		0.005			
143.00	158.00	TU; LAM; FIN <b>Tuf à cendre/lapillis 30°; Laminations parallèles; Grains fins</b> localement massif à grains fin, lamination 30-40° ac, lamines de raphite, légèrement blanchi et chloriteux, altération en calcite, veinules, veines et cheveux de carbonâtes, PY fine irrég diss	144.50	146.00	D002548	1.50	0.025		0.025
			146.00	147.50	D002549	1.50	0.086		0.086
			147.50	149.00	D002551	1.50	0.054		0.054
			149.00	150.50	D002552	1.50	0.302		0.302
			150.50	152.00	D002553	1.50	0.717		0.717
152.00	153.50	FRC <b>Fracturé</b> fragments cm-dm	152.00	153.50	D002554	1.50	0.479		0.479
			153.50	155.00	D002555	1.50	0.391		0.391
155.00	156.50	FRC <b>Fracturé</b> fragments décimétrique à centimétrique	155.00	156.50	D002556	1.50	0.402		0.402
			156.50	158.00	D002557	1.50	0.324		0.324
158.00	161.20	GR; MAS; FIN <b>Grès 40°; Roche massive; Grains fins</b> litage 30-40° ac, légèrement altéré en silice, localement bréchifié, altération en calcite, biotite pervasive, PY automorphe et fine, zone de faille	158.00	159.00	D002558	1.00	0.451		0.451
			159.00	160.00	D002559	1.00	0.424		0.424
			160.00	161.20	D002561	1.20	0.674		0.674
160.70	161.20	FAI <b>Faille 20°</b> zone de faille à fragments bréchifiés à millonitisés							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
161.20	169.50	BA; MAS <b>Basalte 30°; Roche massive</b> localement folié, cheveux 30-40° ac, lamine de graphite, CL+++ , SR++ , amygdules, PY fine diss	161.20	162.50	D002562	1.30	0.086		0.086
			162.50	164.00	D002563	1.50	0.007		0.007
			164.00	165.50	D002564	1.50	0.006		0.006
			165.50	167.00	D002565	1.50	<0.005		0.001
			167.00	168.50	D002566	1.50	0.005		0.005
			168.50	169.50	D002567	1.00	<0.005		0.001
169.50	170.00	NR <b>Carotte perdue</b>							
170.00	288.50	TU; LAM <b>Tuf à cendre/lapillis; Laminations parallèles</b> litage et laminations ± 30-40° ac, localement sub bréchification, veinules veines et cheveux carbonaté, passage de sédiments à graphite, PY fine diss	170.00	171.50	D002568	1.50	1.470		1.470
			171.50	173.00	D002569	1.50	0.206		0.206
			173.00	174.50	D002571	1.50	0.020		0.020
			174.50	176.00	D002572	1.50	0.005		0.005
			176.00	177.50	D002573	1.50	<0.005		0.001
			177.50	179.00	D002574	1.50	0.005		0.005
			179.00	180.50	D002575	1.50	0.005		0.005
			180.50	182.00	D002576	1.50	0.006		0.006
			182.00	183.50	D002578	1.50	0.026		0.026
			183.50	185.00	D002579	1.50	0.020		0.020
			185.00	186.50	D002581	1.50	<0.005		0.001
			186.50	188.00	D002582	1.50	<0.005		0.001
			188.00	189.50	D002583	1.50	<0.005		0.001
			189.50	191.00	D002584	1.50	0.005		0.005
185.20	185.23	FAI <b>Faille 40°</b> boue verdâtre et graphite	191.00	192.50	D002585	1.50	0.005		0.005
			192.50	194.00	D002586	1.50	0.005		0.005
			194.00	195.50	D002587	1.50	<0.005		0.001
			195.50	197.00	D002588	1.50	0.008		0.008
			197.00	198.50	D002589	1.50	0.006		0.006
			198.50	200.00	D002591	1.50	<0.005		0.001
			200.00	201.50	D002592	1.50	0.008		0.008
			201.50	203.00	D002593	1.50	0.032		0.032
			203.00	204.50	D002594	1.50	0.021		0.021
			204.50	206.00	D002595	1.50	0.009		0.009
206.00	207.50	D002596	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	207.50	209.00	D002597	1.50	<0.005		0.001
	209.00	210.50	D002598	1.50	<0.005		0.001
	210.50	212.00	D002599	1.50	<0.005		0.001
	212.00	213.50	D002601	1.50	0.006		0.006
	213.50	215.00	D002602	1.50	<0.005		0.001
	215.00	216.50	D002603	1.50	0.005		0.005
	216.50	218.00	D002604	1.50	<0.005		0.001
	218.00	219.50	D002605	1.50	<0.005		0.001
	219.50	221.00	D002606	1.50	<0.005		0.001
	221.00	222.50	D002607	1.50	<0.005		0.001
	222.50	224.00	D002608	1.50	<0.005		0.001
	224.00	225.50	D002609	1.50	<0.005		0.001
	225.50	227.00	D002611	1.50	<0.005		0.001
	227.00	228.50	D002612	1.50	<0.005		0.001
	228.50	230.00	D002613	1.50	<0.005		0.001
	230.00	231.50	D002614	1.50	0.015		0.015
	231.50	233.00	D002615	1.50	<0.005		0.001
	233.00	234.50	D002616	1.50	0.006		0.006
	234.50	236.00	D002618	1.50	<0.005		0.001
	236.00	237.50	D002619	1.50	0.007		0.007
	237.50	239.00	D002621	1.50	0.005		0.005
	239.00	240.50	D002622	1.50	<0.005		0.001
	240.50	242.00	D002623	1.50	<0.005		0.001
	242.00	243.50	D002624	1.50	0.005		0.005
	243.50	245.00	D002625	1.50	<0.005		0.001
	245.00	246.50	D002626	1.50	<0.005		0.001
	246.50	248.00	D002627	1.50	0.014		0.014
	248.00	249.50	D002628	1.50	<0.005		0.001
	249.50	251.00	D002629	1.50	<0.005		0.001
	251.00	252.50	D002631	1.50	0.008		0.008
	252.50	254.00	D002632	1.50	<0.005		0.001
	254.00	255.50	D002633	1.50	<0.005		0.001
	255.50	257.00	D002634	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				257.00	258.50	D002635	1.50	<0.005		0.001
				258.50	260.00	D002636	1.50	0.006		0.006
				260.00	261.50	D002637	1.50	<0.005		0.001
				261.50	263.00	D002638	1.50	<0.005		0.001
				263.00	264.50	D002639	1.50	<0.005		0.001
				264.50	266.00	D002641	1.50	0.007		0.007
				266.00	267.50	D002642	1.50	<0.005		0.001
				267.50	269.00	D002643	1.50	0.009		0.009
				269.00	270.50	D002644	1.50	<0.005		0.001
				270.50	272.00	D002645	1.50	0.005		0.005
				272.00	273.50	D002646	1.50	0.011		0.011
				273.50	275.00	D002647	1.50	0.032		0.032
				275.00	276.50	D002648	1.50	0.007		0.007
				276.50	278.00	D002649	1.50	0.007		0.007
				278.00	279.50	D002651	1.50	0.008		0.008
				279.50	281.00	D002652	1.50	<0.005		0.001
				281.00	282.50	D002653	1.50	0.008		0.008
				282.50	284.00	D002654	1.50	0.009		0.009
				284.00	285.50	D002655	1.50	<0.005		0.001
				285.50	287.00	D002656	1.50	<0.005		0.001
				287.00	288.50	D002658	1.50	0.006		0.006
288.50	297.00	GR		288.50	290.00	D002659	1.50	0.013		0.013
		<b>Grès</b>		290.00	291.50	D002661	1.50	0.020		0.020
		massive légèrement altéré en silice, localement bréchique à sub		291.50	293.00	D002662	1.50	0.051		0.051
		bréchique, biotite pervasive, chlorite, calcite, veines de calcite PY fine		293.00	294.50	D002663	1.50	0.032		0.032
		diss		294.50	296.00	D002664	1.50	0.792		0.792
				296.00	297.00	D002665	1.00	0.303		0.303
288.50	295.50	GR; BRC								
		<b>Grès; Brèche de coulée</b>								
		fragments anguleux ou sub arrondi 0.4-3 cm, calcite, biotite,								
		cheveux et veinules carbonat.é, légère silicification, PY fine diss								
297.00	298.20	NR								
		<b>Carotte perdue</b>								
		grindé								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
298.20	330.60	TU; FIN; LAM <b>Tuf à cendre/lapillis; Grains fins; Laminations parallèles</b> litage 30-40° ac, localement cisailé, lamines de graphite, veines de QZ et calcite, CL+++; calcite, PYfine irrég diss	298.20	299.50	D002666	1.30	0.030		0.030
			299.50	301.00	D002667	1.50	0.009		0.009
			301.00	302.50	D002668	1.50	<0.005		0.001
			302.50	304.00	D002669	1.50	<0.005		0.001
			304.00	305.50	D002671	1.50	0.007		0.007
			305.50	307.00	D002672	1.50	0.510		0.510
			307.00	308.50	D002673	1.50	0.008		0.008
			308.50	310.00	D002674	1.50	<0.005		0.001
			310.00	311.50	D002675	1.50	0.005		0.005
			311.50	313.00	D002676	1.50	0.046		0.046
			313.00	314.50	D002677	1.50	0.016		0.016
			314.50	316.00	D002678	1.50	0.027		0.027
			316.00	317.50	D002679	1.50	<0.005		0.001
			317.50	319.00	D002681	1.50	0.009		0.009
			319.00	320.50	D002682	1.50	<0.005		0.001
			320.50	322.00	D002683	1.50	<0.005		0.001
			322.00	323.50	D002684	1.50	<0.005		0.001
			323.50	325.00	D002685	1.50	<0.005		0.001
			325.00	326.50	D002686	1.50	<0.005		0.001
			326.50	328.00	D002687	1.50	<0.005		0.001
328.00	329.50	D002688	1.50	<0.005		0.001			
329.50	330.60	D002689	1.10	<0.005		0.001			
330.60	331.70	D002691	1.10	0.010		0.010			
330.60	331.70								
331.70		ST; FIN; LAM <b>Siltstone 30°; Grains fins; Laminations parallèles</b> litage et laminations 30-40° ac lentilles de graphite, fragments cm, PY en amas fin diss							
331.70		Fin du sondage Nombre d'échantillons : 203 Nombre d'échantillons QAQC : 28 Longueur totale échantillonnée : 297.00							



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
45.00	46.50	D002470	D002469	1.50	0.007	0.007
57.50	59.00	D002480	A3	1.50	0.632	0.632
70.50	72.00	D002490	D002489	1.50	0.012	0.012
79.50	80.50	D002497	M1	1.00	<0.005	0.001
82.00	83.50	D002500	B4	1.50	2.620	2.620
95.00	96.00	D002510	D002509	1.00	0.009	0.009
108.50	110.00	D002520	C4	1.50		
121.50	123.00	D002530	D002529	1.50	0.006	0.006
130.50	132.00	D002537	M1	1.50	<0.005	0.001
133.50	133.50	D002540	D2	0.00	0.866	0.866
146.00	147.50	D002550	D002549	1.50	0.094	0.094
159.00	159.00	D002560	F2	0.00	8.370	8.370
171.50	173.00	D002570	D002569	1.50	0.177	0.177
180.50	182.00	D002577	M1	1.50	<0.005	0.001
183.50	185.00	D002580	G2	1.50	3.930	3.930
197.00	198.50	D002590	D002589	1.50	0.007	0.007
210.50	210.50	D002600	H	0.00	1.040	1.040
224.00	225.50	D002610	D002609	1.50	<0.005	0.001
233.00	234.50	D002617	M1	1.50	<0.005	0.001
236.00	237.50	D002620	A3	1.50	0.609	0.609
249.50	251.00	D002630	D002629	1.50	<0.005	0.001
263.00	264.50	D002640	B4	1.50	2.520	2.520
276.50	278.00	D002650	D002649	1.50	0.006	0.006
285.50	287.00	D002657	M1	1.50	<0.005	0.001
288.50	288.50	D002660	C4	0.00	1.320	1.320
302.50	304.00	D002670	D002669	1.50	<0.005	0.001
316.00	316.00	D002680	D2	0.00	0.881	0.881
329.50	330.60	D002690	D002689	1.10	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-163**

Titre minier :

Section :                      630000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-17

Date de description :

Au :                      2010-04-23

Collet

UTM

Azimut :                0.00°

Plongée :              -68.00°

Longueur :            326.00 m

Est                      630 000.2

Nord                    5 374 200.4

Élévation              282.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	296.10°	-68.30°	Oui
Reflex	8.00	160.30°	-67.10°	Oui
Reflex	11.00	55.20°	-66.80°	Oui
Reflex	14.00	328.20°	-66.40°	Oui
Reflex	17.00	35.90°	-66.20°	Oui
Reflex	20.00	179.30°	-66.20°	Oui
Reflex	23.00	329.10°	-65.80°	Oui
Reflex	26.00	353.80°	-65.60°	Oui
Reflex	29.00	127.50°	-65.10°	Oui
Reflex	32.00	1.40°	-65.00°	Non
Reflex	35.00	1.90°	-65.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.70°	-65.10°	Non
Reflex	41.00	1.90°	-65.10°	Non
Reflex	44.00	1.90°	-65.20°	Non
Reflex	47.00	2.20°	-65.20°	Non
Reflex	50.00	2.10°	-65.20°	Non
Reflex	53.00	3.20°	-65.10°	Non
Reflex	56.00	2.50°	-65.00°	Non
Reflex	59.00	2.30°	-65.00°	Non
Reflex	62.00	2.60°	-65.00°	Non
Reflex	65.00	1.90°	-65.10°	Non
Reflex	68.00	2.60°	-65.10°	Non
Reflex	71.00	2.50°	-65.00°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.50°	-64.90°	Non
Reflex	77.00	2.40°	-64.90°	Non
Reflex	80.00	2.70°	-64.90°	Non
Reflex	83.00	2.60°	-65.00°	Non
Reflex	86.00	1.40°	-65.00°	Non
Reflex	89.00	1.80°	-65.40°	Non
Reflex	92.00	1.40°	-65.30°	Non
Reflex	95.00	1.90°	-65.50°	Non
Reflex	98.00	2.10°	-65.70°	Non
Reflex	101.00	1.70°	-65.90°	Non
Reflex	104.00	1.80°	-65.60°	Non
Reflex	107.00	2.70°	-65.90°	Non
Reflex	110.00	2.20°	-65.80°	Non
Reflex	113.00	2.40°	-66.20°	Non
Reflex	116.00	1.00°	-65.90°	Non
Reflex	119.00	1.40°	-66.20°	Non
Reflex	122.00	1.30°	-66.20°	Non
Reflex	125.00	0.80°	-66.10°	Non
Reflex	128.00	1.50°	-66.20°	Non
Reflex	131.00	1.10°	-66.20°	Non
Reflex	134.00	0.80°	-66.30°	Non
Reflex	137.00	0.70°	-66.40°	Non
Reflex	140.00	0.90°	-66.60°	Non
Reflex	143.00	0.70°	-66.40°	Non
Reflex	146.00	1.60°	-66.80°	Non
Reflex	149.00	1.20°	-66.70°	Non
Reflex	152.00	0.80°	-66.70°	Non
Reflex	155.00	1.30°	-66.90°	Non
Reflex	158.00	1.30°	-67.00°	Non
Reflex	161.00	1.00°	-66.80°	Non
Reflex	164.00	1.00°	-66.80°	Non
Reflex	167.00	0.80°	-66.80°	Non
Reflex	170.00	0.00°	-66.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	0.10°	-66.80°	Non
Reflex	176.00	0.10°	-66.90°	Non
Reflex	179.00	359.50°	-66.80°	Non
Reflex	182.00	359.40°	-66.80°	Non
Reflex	185.00	359.40°	-66.90°	Non
Reflex	188.00	359.90°	-67.20°	Non
Reflex	191.00	359.30°	-67.20°	Non
Reflex	194.00	358.70°	-67.20°	Non
Reflex	197.00	358.20°	-67.20°	Non
Reflex	200.00	358.70°	-67.40°	Non
Reflex	203.00	358.80°	-67.30°	Non
Reflex	206.00	357.80°	-67.30°	Non
Reflex	209.00	357.50°	-67.10°	Non
Reflex	212.00	357.80°	-67.30°	Non
Reflex	215.00	356.80°	-67.20°	Non
Reflex	218.00	357.40°	-67.30°	Non
Reflex	221.00	356.70°	-67.20°	Non
Reflex	224.00	357.10°	-67.40°	Non
Reflex	227.00	356.80°	-67.40°	Non
Reflex	230.00	356.10°	-67.30°	Non
Reflex	233.00	355.90°	-67.30°	Non
Reflex	236.00	356.40°	-67.30°	Non
Reflex	239.00	355.30°	-67.30°	Non
Reflex	242.00	355.70°	-67.30°	Non
Reflex	245.00	355.20°	-67.30°	Non
Reflex	248.00	355.20°	-67.30°	Non
Reflex	251.00	355.70°	-67.40°	Non
Reflex	254.00	355.20°	-67.30°	Non
Reflex	257.00	354.00°	-67.30°	Non
Reflex	260.00	354.70°	-67.30°	Non
Reflex	263.00	354.60°	-67.20°	Non
Reflex	266.00	354.20°	-67.20°	Non
Reflex	269.00	353.10°	-67.20°	Non

Corporation Minière Osisko Div. Exploration

Déviatiion

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	353.20°	-67.20°	Non					
Reflex	275.00	353.00°	-67.30°	Non					
Reflex	278.00	353.30°	-67.40°	Non					
Reflex	281.00	353.00°	-67.30°	Non					
Reflex	284.00	352.40°	-67.20°	Non					
Reflex	287.00	352.40°	-67.30°	Non					
Reflex	290.00	351.70°	-67.20°	Non					
Reflex	293.00	351.50°	-67.10°	Non					
Reflex	296.00	350.60°	-67.00°	Non					
Reflex	299.00	350.90°	-67.00°	Non					
Reflex	302.00	350.00°	-67.00°	Non					
Reflex	305.00	350.60°	-67.10°	Non					
Reflex	308.00	350.00°	-67.20°	Non					
Reflex	311.00	349.60°	-67.00°	Non					
Reflex	314.00	349.30°	-67.00°	Non					
Reflex	317.00	350.00°	-67.20°	Non					
Reflex	320.00	349.00°	-67.10°	Non					
Reflex	323.00	349.90°	-67.40°	Non					
Reflex	326.00	349.80°	-67.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	31.50	MT <b>Mort-terrain</b>							
31.50	38.50	UM; APH <b>Ultramaïfite serpentinisée; Aphanitique</b> Ultramaïfite serpentinisée aphanitique avec passage schisteux.	31.50	33.00	D008518	1.50	<0.005		0.001
			33.00	34.00	D008519	1.00	0.006		0.006
			34.00	35.50	D008520	1.50	<0.005		0.001
			35.50	37.00	D008521	1.50	<0.005		0.001
			37.00	38.50	D008522	1.50	<0.005		0.001
38.50	53.10	GR; FIN <b>Grès; Grains fins</b> Grès à grains fins.	38.50	40.00	D008523	1.50	0.008		0.008
			40.00	41.50	D008524	1.50	0.013		0.013
			41.50	43.00	D008525	1.50	0.005		0.005
			43.00	44.50	D008526	1.50	0.008		0.008
			44.50	46.00	D008528	1.50	0.015		0.015
			46.00	47.50	D008529	1.50	0.005		0.005
			47.50	49.00	D008530	1.50	<0.005		0.001
			49.00	50.50	D008531	1.50	<0.005		0.001
			50.50	52.00	D008532	1.50	0.088		0.088
			52.00	53.10	D008533	1.10	0.101		0.101
53.10	80.00	BA; MAS; APH <b>Basalte 55*; Roche massive; Aphanitique</b> Basalte massive et aphanitique.	53.10	54.50	D008534	1.40	0.190		0.190
			54.50	56.00	D008535	1.50	0.086		0.086
			56.00	57.50	D008536	1.50	0.049		0.049
			57.50	59.00	D008538	1.50	0.063		0.063
			59.00	60.50	D008539	1.50	0.074		0.074
			60.50	62.00	D008540	1.50	0.010		0.010
			62.00	63.50	D008541	1.50	0.019		0.019
			63.50	65.00	D008543	1.50	0.016		0.016
			65.00	66.50	D008544	1.50	0.055		0.055
			66.50	68.00	D008545	1.50	0.119		0.119
			68.00	69.50	D008546	1.50	0.107		0.107
			69.50	71.00	D008548	1.50	0.095		0.095
			71.00	72.50	D008549	1.50	0.189		0.189
			72.50	74.00	D008550	1.50	1.175		1.175
74.00	75.50	D008551	1.50	0.317		0.317			
75.50	77.00	D008552	1.50	0.106		0.106			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
80.00	88.50	GR; FIN; MTY <b>Grès; Grains fins; Grains moyens</b> Grès à grains fins à moyens avec passage de bande graphitique.	77.00	78.50	D008553	1.50	0.013		0.013
			78.50	80.00	D008554	1.50	0.088		0.088
			80.00	81.50	D008555	1.50	0.100		0.100
			81.50	83.00	D008556	1.50	0.020		0.020
			83.00	84.50	D008558	1.50	0.943		0.943
			84.50	86.00	D008559	1.50	0.262		0.262
			86.00	87.50	D008560	1.50	0.183		0.183
			87.50	88.50	D008561	1.00	0.450		0.450
88.50	91.50	GW; MAS <b>Grauwacke; Roche massive</b> Grauwacke massive avec passage graphiteuse.	88.50	90.00	D008562	1.50	0.170		0.170
			90.00	91.50	D008563	1.50	0.079		0.079
91.50	102.50	GR; FIN; MTY <b>Grès; Grains fins; Grains moyens</b> Grès à grains fins à moyens avec passage graphiteux.	91.50	93.00	D008564	1.50	0.113		0.113
			93.00	94.50	D008565	1.50	0.038		0.038
			94.50	96.00	D008566	1.50	0.262		0.262
			96.00	97.00	D008568	1.00	0.406		0.406
			97.00	98.50	D008569	1.50	0.552		0.552
98.00	104.00	FRC <b>Fracturé</b> Zone fracturée qui est possiblement une zone de faille.	98.50	100.00	D008570	1.50	0.322		0.322
			100.00	101.00	D008571	1.00	0.053		0.053
			101.00	102.50	D008572	1.50	0.290		0.290
			102.50	104.20	D008573	1.70	1.020		1.020
102.50	104.20	GW; MAS <b>Grauwacke 35°; Roche massive</b> Grauwacke avec de grains très fins avec de passage graphiteuse.							
104.20	215.20	GR; FIN; MTY <b>Grès; Grains fins; Grains moyens</b> Grès à grains fins à grains moyens, avec passage brèche interferrationnelle à fragments Xmm à Xcm dans une matrice graphitique et avec de passage lité.	104.20	105.50	D008574	1.30	0.012		0.012
			105.50	107.00	D008575	1.50	0.007		0.007
			107.00	108.50	D008576	1.50	<0.005		0.001
			108.50	110.00	D008578	1.50	0.005		0.005
			110.00	111.50	D008579	1.50	<0.005		0.001
			111.50	113.00	D008580	1.50	0.264		0.264
			113.00	114.50	D008581	1.50	0.110		0.110
			114.50	116.00	D008583	1.50	0.456		0.456
			116.00	117.50	D008584	1.50	0.322		0.322
			117.50	119.00	D008585	1.50	0.341		0.341
			119.00	120.50	D008586	1.50	0.299		0.299
120.50	122.00	D008588	1.50	0.150		0.150			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	122.00	123.50	D008589	1.50	0.199		0.199
	123.50	125.00	D008590	1.50	0.375		0.375
	125.00	126.50	D008591	1.50	0.390		0.390
	126.50	128.00	D008592	1.50	0.216		0.216
	128.00	129.50	D008593	1.50	0.099		0.099
	129.50	131.00	D008594	1.50	0.243		0.243
	131.00	132.50	D008595	1.50	0.152		0.152
	132.50	134.00	D008596	1.50	0.259		0.259
	134.00	135.50	D008598	1.50	0.493		0.493
	135.50	137.00	D008599	1.50	1.750		1.750
	137.00	138.50	D008600	1.50	0.441		0.441
	138.50	140.00	D008601	1.50	0.778		0.778
	140.00	141.50	D008602	1.50	0.634		0.634
	141.50	143.00	D008603	1.50	0.178		0.178
	143.00	144.50	D008604	1.50	0.234		0.234
	144.50	146.00	D008605	1.50	0.383		0.383
	146.00	147.50	D008606	1.50	0.196		0.196
	147.50	149.00	D008608	1.50	0.353		0.353
	149.00	150.50	D008609	1.50	0.247		0.247
	150.50	152.00	D008610	1.50	0.210		0.210
	152.00	153.50	D008611	1.50	0.265		0.265
	153.50	155.00	D008612	1.50	0.047		0.047
	155.00	156.50	D008613	1.50	0.073		0.073
	156.50	158.00	D008614	1.50	0.301		0.301
	158.00	159.50	D008615	1.50	0.064		0.064
	159.50	161.00	D008616	1.50	0.173		0.173
	161.00	162.50	D008618	1.50	0.059		0.059
	162.50	164.00	D008619	1.50	0.053		0.053
	164.00	165.50	D008620	1.50	<0.005		0.001
	165.50	167.00	D008621	1.50	0.160		0.160
	167.00	168.50	D008623	1.50	0.281		0.281
	168.50	170.00	D008624	1.50	0.188		0.188
	170.00	171.50	D008625	1.50	0.223		0.223





Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
223.80	326.00	GR; FIN; MTY  <b>Grès; Grains fins; Grains moyens</b> Grès, grains fins à moyens, avec passage brèche interformationnelle à fragments Xmm à Xcm dans une matrice graphitique .	221.00	222.50	D008664	1.50	<0.005		0.001
			222.50	223.80	D008665	1.30	<0.005		0.001
			223.80	225.50	D008666	1.70	0.022		0.022
			225.50	227.00	D008668	1.50	0.026		0.026
			227.00	228.50	D008669	1.50	0.033		0.033
			228.50	230.00	D008670	1.50	<0.005		0.001
			230.00	231.50	D008671	1.50	<0.005		0.001
			231.50	233.00	D008672	1.50	<0.005		0.001
			233.00	234.50	D008673	1.50	<0.005		0.001
			234.50	236.00	D008674	1.50	<0.005		0.001
			236.00	237.50	D008675	1.50	<0.005		0.001
			237.50	239.00	D008676	1.50	<0.005		0.001
			239.00	240.50	D008678	1.50	<0.005		0.001
			240.50	242.00	D008679	1.50	0.006		0.006
			242.00	243.50	D008680	1.50	0.124		0.124
			243.50	245.00	D008681	1.50	0.041		0.041
			245.00	246.50	D008682	1.50	0.015		0.015
			246.50	248.00	D008683	1.50	0.012		0.012
			248.00	249.50	D008684	1.50	0.011		0.011
			249.50	251.00	D008685	1.50	<0.005		0.001
			251.00	252.50	D008686	1.50	0.007		0.007
			252.50	254.00	D008688	1.50	0.006		0.006
			254.00	255.50	D008689	1.50	0.008		0.008
			255.50	257.00	D008690	1.50	<0.005		0.001
			257.00	258.50	D008691	1.50	<0.005		0.001
			258.50	260.00	D008692	1.50	<0.005		0.001
			260.00	261.50	D008693	1.50	<0.005		0.001
261.50	263.00	D008694	1.50	<0.005		0.001			
263.00	264.50	D008695	1.50	<0.005		0.001			
264.50	266.00	D008696	1.50	<0.005		0.001			
266.00	267.50	D008698	1.50	<0.005		0.001			
267.50	269.00	D008699	1.50	<0.005		0.001			
269.00	270.50	D008700	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	270.50	272.00	D008701	1.50	<0.005		0.001
	272.00	273.50	D008703	1.50	<0.005		0.001
	273.50	275.00	D008704	1.50	<0.005		0.001
	275.00	276.50	D008705	1.50	<0.005		0.001
	276.50	278.00	D008706	1.50	<0.005		0.001
	278.00	279.50	D008708	1.50	<0.005		0.001
	279.50	281.00	D008709	1.50	0.005		0.005
	281.00	282.50	D008710	1.50	<0.005		0.001
	282.50	284.00	D008711	1.50	<0.005		0.001
	284.00	285.50	D008712	1.50	<0.005		0.001
	285.50	287.00	D008713	1.50	<0.005		0.001
	287.00	288.50	D008714	1.50	0.005		0.005
	288.50	290.00	D008715	1.50	<0.005		0.001
	290.00	291.50	D008716	1.50	<0.005		0.001
	291.50	293.00	D008718	1.50	0.005		0.005
	293.00	294.50	D008719	1.50	<0.005		0.001
	294.50	296.00	D008720	1.50	<0.005		0.001
	296.00	297.50	D008721	1.50	<0.005		0.001
	297.50	299.00	D008722	1.50	<0.005		0.001
	299.00	300.50	D008723	1.50	<0.005		0.001
	300.50	302.00	D008724	1.50	<0.005		0.001
	302.00	303.50	D008725	1.50	<0.005		0.001
	303.50	305.00	D008726	1.50	0.005		0.005
	305.00	306.50	D008728	1.50	0.006		0.006
	306.50	308.00	D008729	1.50	0.006		0.006
	308.00	309.50	D008730	1.50	<0.005		0.001
	309.50	311.00	D008731	1.50	<0.005		0.001
	311.00	312.50	D008732	1.50	<0.005		0.001
	312.50	314.00	D008733	1.50	0.005		0.005
	314.00	315.50	D008734	1.50	0.005		0.005
	315.50	317.00	D008735	1.50	<0.005		0.001
	317.00	318.50	D008736	1.50	<0.005		0.001
	318.50	320.00	D008738	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	320.00	321.50	D008739	1.50	<0.005		0.001
	321.50	323.00	D008740	1.50	<0.005		0.001
	323.00	324.50	D008741	1.50	<0.005		0.001
	324.50	326.00	D008743	1.50	<0.005		0.001
<p>326.00 Fin du sondage            Nombre d'échantillons : 198            Nombre d'échantillons QAQC : 28            Longueur totale échantillonnée : 294.50</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
43.00	44.50	D008527	A3	1.50	0.597	0.597
56.00	57.00	D008537	D008536	1.00	0.114	0.114
62.00	63.50	D008542	M1	1.50	<0.005	0.001
68.00	69.50	D008547	G2	1.50	4.150	4.150
81.50	83.00	D008557	D008556	1.50	0.022	0.022
94.50	96.00	D008567	C4	1.50	1.375	1.375
107.00	108.50	D008577	D008576	1.50	<0.005	0.001
113.00	114.50	D008582	M1	1.50	<0.005	0.001
119.00	120.50	D008587	D2	1.50	0.861	0.861
132.50	134.00	D008597	D008596	1.50	0.291	0.291
146.00	147.50	D008607	F2	1.50	8.490	8.490
159.50	161.00	D008617	D008616	1.50	0.176	0.176
165.50	167.00	D008622	M1	1.50	<0.005	0.001
171.50	173.00	D008627	G2	1.50	4.200	4.200
185.00	186.50	D008637	D008636	1.50	0.525	0.525
198.50	200.00	D008647	H	1.50	0.965	0.965
212.00	213.50	D008657	D008656	1.50	0.664	0.664
218.00	219.50	D008662	M1	1.50	<0.005	0.001
223.80	225.50	D008667	A3	1.70	0.514	0.514
237.50	239.00	D008677	D008676	1.50	<0.005	0.001
251.00	252.50	D008687	B4	1.50	2.520	2.520
264.50	266.00	D008697	D008696	1.50	<0.005	0.001
270.50	272.00	D008702	M1	1.50	<0.005	0.001
276.50	278.00	D008707	C4	1.50	1.340	1.340
290.00	291.50	D008717	D008716	1.50	<0.005	0.001
303.50	305.00	D008727	D2	1.50	0.895	0.895
317.00	318.50	D008737	D008736	1.50	<0.005	0.001
323.00	324.50	D008742	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-164</b>	Titre minier :	Section :	630000
	Canton :	Niveau :	
	Rang :	Place de travail :	
Foré par : Bradley	Lot :		
Décrit par : David RUHARA	Du : 2010-04-23	Date de description :	
	Au : 2010-04-27		

Collet

Azimut : 0.00°		UTM						
Plongée : -77.00°		<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">Est</td> <td style="width: 85%;">630 000.2</td> </tr> <tr> <td>Nord</td> <td>5 374 200.2</td> </tr> <tr> <td>Élévation</td> <td>282.9</td> </tr> </table>	Est	630 000.2	Nord	5 374 200.2	Élévation	282.9
Est	630 000.2							
Nord	5 374 200.2							
Élévation	282.9							
Longueur : 178.50 m								

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide

Description

Dimension de la carotte : NQ	Cimenté : Non	Entreposé : Oui
------------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	27.50	MT <b>Mort-terrain</b>						
27.50	64.00	UM; APH <b>Ultramaïfite serpentinisée; Aphanitique</b> ultramaïfite serpentinisée aphanitique avec de passage schisteux.	27.50	29.00	D008403	1.50	0.007	0.007
			29.00	30.50	D008404	1.50	<0.005	0.001
			30.50	32.00	D008405	1.50	<0.005	0.001
			32.00	33.50	D008406	1.50	<0.005	0.001
			33.50	35.00	D008408	1.50	<0.005	0.001
			35.00	36.50	D008409	1.50	<0.005	0.001
			36.50	38.00	D008410	1.50	<0.005	0.001
			38.00	39.50	D008411	1.50	<0.005	0.001
			39.50	41.00	D008412	1.50	0.096	0.096
			41.00	42.50	D008413	1.50	0.121	0.121
			42.50	44.00	D008414	1.50	0.007	0.007
			44.00	45.50	D008415	1.50	<0.005	0.001
			45.50	47.00	D008416	1.50	<0.005	0.001
			47.00	48.50	D008418	1.50	<0.005	0.001
			48.50	50.00	D008419	1.50	0.068	0.068
			50.00	51.50	D008420	1.50	0.008	0.008
			51.50	53.00	D008421	1.50	0.026	0.026
			53.00	54.50	D008423	1.50	0.026	0.026
			54.50	56.00	D008424	1.50	<0.005	0.001
			56.00	57.50	D008425	1.50	<0.005	0.001
			57.50	59.00	D008426	1.50	<0.005	0.001
			59.00	60.50	D008428	1.50	<0.005	0.001
			60.50	62.00	D008429	1.50	<0.005	0.001
			62.00	63.00	D008430	1.00	<0.005	0.001
			63.00	64.00	D008431	1.00	0.043	0.043
64.00	65.00	NR <b>Carotte perdue</b>						
65.00	141.80	UM; APH <b>Ultramaïfite serpentinisée; Aphanitique</b> Ultramaïfite serpentinisée aphanitique avec de passage schisteux.	65.00	66.50	D008432	1.50	<0.005	0.001
			66.50	68.00	D008433	1.50	<0.005	0.001
			68.00	69.50	D008434	1.50	0.062	0.062
			69.50	71.00	D008435	1.50	0.104	0.104
			71.00	72.50	D008436	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	72.50	74.00	D008438	1.50	<0.005		0.001
	74.00	75.50	D008439	1.50	<0.005		0.001
	75.50	77.00	D008440	1.50	<0.005		0.001
	77.00	78.50	D008441	1.50	0.010		0.010
	78.50	80.00	D008442	1.50	<0.005		0.001
	80.00	81.50	D008443	1.50	<0.005		0.001
	81.50	83.00	D008444	1.50	0.018		0.018
	83.00	84.50	D008445	1.50	0.191		0.191
	84.50	86.00	D008446	1.50	0.020		0.020
	86.00	87.50	D008448	1.50	<0.005		0.001
	87.50	89.00	D008449	1.50	0.007		0.007
	89.00	90.50	D008450	1.50	0.007		0.007
	90.50	92.00	D008451	1.50	0.007		0.007
	92.00	93.50	D008452	1.50	0.024		0.024
	93.50	95.00	D008453	1.50	<0.005		0.001
	95.00	96.50	D008454	1.50	0.005		0.005
	96.50	98.00	D008455	1.50	0.008		0.008
	98.00	99.50	D008456	1.50	0.009		0.009
	99.50	101.00	D008458	1.50	<0.005		0.001
	101.00	102.50	D008459	1.50	<0.005		0.001
	102.50	104.00	D008460	1.50	<0.005		0.001
	104.00	105.50	D008461	1.50	0.006		0.006
	105.50	107.00	D008463	1.50	<0.005		0.001
	107.00	108.50	D008464	1.50	<0.005		0.001
	108.50	110.00	D008465	1.50	0.010		0.010
	110.00	111.50	D008466	1.50	<0.005		0.001
	111.50	113.00	D008468	1.50	0.005		0.005
	113.00	114.50	D008469	1.50	<0.005		0.001
	114.50	116.00	D008470	1.50	<0.005		0.001
	116.00	117.50	D008471	1.50	<0.005		0.001
	117.50	119.00	D008472	1.50	<0.005		0.001
	119.00	120.50	D008473	1.50	<0.005		0.001
	120.50	122.00	D008474	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			122.00	123.50	D008475	1.50	<0.005		0.001
			123.50	125.00	D008476	1.50	0.005		0.005
			125.00	126.50	D008478	1.50	0.005		0.005
			126.50	128.00	D008479	1.50	<0.005		0.001
			128.00	129.50	D008480	1.50	<0.005		0.001
			129.50	131.00	D008481	1.50	<0.005		0.001
			131.00	132.50	D008482	1.50	<0.005		0.001
			132.50	134.00	D008483	1.50	<0.005		0.001
			134.00	135.50	D008484	1.50	0.005		0.005
			135.50	137.00	D008485	1.50	<0.005		0.001
			137.00	138.50	D008486	1.50	<0.005		0.001
			138.50	140.10	D008488	1.60	0.008		0.008
			140.10	141.80	D008489	1.70	0.009		0.009
141.80	142.40	NR							
		<b>Carotte perdue</b>							
142.40	178.50	UM; APH	142.40	144.00	D008490	1.60	<0.005		0.001
		<b>Ultramaïfite serpentinisée; Aphanitique</b>	144.00	145.50	D008491	1.50	0.007		0.007
		Ultramaïfite serpentinisée aphanitique avec passage schisteux.	145.50	147.00	D008492	1.50	<0.005		0.001
			147.00	148.50	D008493	1.50	0.005		0.005
			148.50	150.00	D008494	1.50	<0.005		0.001
			150.00	151.50	D008495	1.50	0.005		0.005
			151.50	153.00	D008496	1.50	<0.005		0.001
			153.00	154.50	D008498	1.50	<0.005		0.001
			154.50	156.00	D008499	1.50	0.005		0.005
			156.00	157.50	D008500	1.50	<0.005		0.001
			157.50	159.00	D008501	1.50	<0.005		0.001
			159.00	160.50	D008503	1.50	<0.005		0.001
			160.50	162.00	D008504	1.50	<0.005		0.001
			162.00	163.50	D008505	1.50	<0.005		0.001
			163.50	165.00	D008506	1.50	0.005		0.005
			165.00	166.50	D008508	1.50	0.007		0.007
			166.50	168.00	D008509	1.50	<0.005		0.001
			168.00	169.50	D008510	1.50	<0.005		0.001
			169.50	171.00	D008511	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	171.00	172.50	D008512	1.50	0.017		0.017
	172.50	174.00	D008513	1.50	<0.005		0.001
	174.00	175.50	D008514	1.50	0.011		0.011
	175.50	177.00	D008515	1.50	<0.005		0.001
	177.00	178.50	D008516	1.50	<0.005		0.001
<p>178.50      Fin du sondage                      Nombre d'échantillons : 100                      Nombre d'échantillons QAQC : 15                      Longueur totale échantillonnée : 149.40</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
32.00	33.50	D008407	B4	1.50	2.590	2.590
45.50	47.00	D008417	D008416	1.50	0.007	0.007
51.50	53.00	D008422	M1	1.50	<0.005	0.001
57.50	59.00	D008427	C4	1.50	1.240	1.240
71.00	72.50	D008437	D008436	1.50	0.009	0.009
84.50	86.00	D008447	D2	1.50	0.843	0.843
98.00	99.50	D008457	D008456	1.50	<0.005	0.001
104.00	105.50	D008462	M1	1.50	<0.005	0.001
110.00	111.50	D008467	F2	1.50	7.910	7.910
123.50	125.00	D008477	D008476	1.50	0.006	0.006
137.00	138.50	D008487	G2	1.50	4.250	4.250
151.50	153.00	D008497	D008496	1.50	0.006	0.006
157.50	159.00	D008502	M1	1.50	<0.005	0.001
163.50	165.00	D008507	H	1.50	0.991	0.991
177.00	178.50	D008517	D008516	1.50	0.007	0.007

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-164B**

Titre minier :

Section :                      630000

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    David RUHARA

Lot :

Du :                              2010-05-29

Date de description :

Au :                              2010-06-03

Collet

UTM

Azimut :                        0.00°

Plongée :                       -68.00°

Longueur :                    338.00 m

Est                              630 000.0

Nord                            5 374 136.6

Élévation                      287.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	15.20°	-66.80°	Oui
Reflex	8.00	341.40°	-65.60°	Oui
Reflex	11.00	356.50°	-65.30°	Oui
Reflex	14.00	336.60°	-65.60°	Oui
Reflex	17.00	353.70°	-66.60°	Oui
Reflex	20.00	344.50°	-67.20°	Oui
Reflex	23.00	323.60°	-67.20°	Oui
Reflex	26.00	312.80°	-66.70°	Oui
Reflex	29.00	339.10°	-66.60°	Oui
Reflex	32.00	333.90°	-66.60°	Oui
Reflex	35.00	330.90°	-66.20°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	185.90°	-65.90°	Oui
Reflex	41.00	352.20°	-65.00°	Non
Reflex	44.00	351.80°	-64.60°	Non
Reflex	47.00	351.80°	-64.40°	Non
Reflex	50.00	351.70°	-64.20°	Non
Reflex	53.00	351.70°	-63.90°	Non
Reflex	56.00	351.70°	-63.60°	Non
Reflex	59.00	351.20°	-63.30°	Non
Reflex	62.00	351.00°	-63.20°	Non
Reflex	65.00	350.90°	-63.10°	Non
Reflex	68.00	350.80°	-62.90°	Non
Reflex	71.00	350.50°	-62.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	38.20	MT <b>Mort-terrain</b>						
38.20	81.00	GR; FIN; MTY <b>Grès; Grains fins; Grains moyens</b> Roche litée, grains fins à grains moyens et cisailée différentiellemt.	38.20	39.50	D019630	1.30	0.010	0.010
			39.50	41.00	D019631	1.50	0.006	0.006
			41.00	42.50	D019632	1.50	0.008	0.008
			42.50	44.00	D019633	1.50	0.008	0.008
			44.00	45.50	D019634	1.50	0.009	0.009
			45.50	47.00	D019635	1.50	0.011	0.011
			47.00	48.50	D019636	1.50	0.007	0.007
			48.50	50.00	D019638	1.50	0.008	0.008
			50.00	51.50	D019639	1.50	0.008	0.008
			51.50	53.00	D019640	1.50	0.010	0.010
			53.00	54.50	D019641	1.50	0.019	0.019
			54.50	56.00	D019642	1.50	0.011	0.011
			56.00	57.50	D019643	1.50	0.006	0.006
			57.50	59.00	D019644	1.50	0.064	0.064
			59.00	60.50	D019645	1.50	0.092	0.092
			60.50	62.00	D019646	1.50	0.060	0.060
			62.00	63.50	D019648	1.50	0.042	0.042
63.50	81.00	CIS; FRC <b>Cisaillement; Fracturé</b> Lité et fortement cisailé et fracturé au contact infér.	63.50	65.00	D019649	1.50	0.027	0.027
			65.00	66.50	D019650	1.50	0.083	0.083
			66.50	68.00	D019651	1.50	0.021	0.021
			68.00	69.50	D019652	1.50	0.028	0.028
			69.50	71.00	D019653	1.50	0.085	0.085
			71.00	72.50	D019654	1.50	0.009	0.009
			72.50	74.00	D019655	1.50	0.018	0.018
			74.00	75.50	D019656	1.50	0.047	0.047
			75.50	77.00	D019658	1.50	0.040	0.040
			77.00	78.50	D019659	1.50	0.011	0.011
			78.50	80.00	D019660	1.50	<0.005	0.001
			80.00	81.00	D019661	1.00	0.007	0.007
81.00	81.90	NR <b>Carotte perdue</b>						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
81.90	185.50	GR; FIN; MTY <b>Grès; Grains fins; Grains moyens</b> Litée, grains fins à grains moyens, et cisailé.	81.90	83.50	D019663	1.60	0.040		0.040
			83.50	85.00	D019664	1.50	0.006		0.006
			85.00	86.50	D019665	1.50	<0.005		0.001
			86.50	88.00	D019666	1.50	<0.005		0.001
			88.00	89.50	D019668	1.50	0.022		0.022
			89.50	91.00	D019669	1.50	0.138		0.138
			91.00	92.50	D019670	1.50	0.036		0.036
			92.50	94.00	D019671	1.50	0.009		0.009
			94.00	95.50	D019672	1.50	0.180		0.180
			95.50	97.00	D019673	1.50	0.132		0.132
			97.00	98.50	D019674	1.50	0.006		0.006
			98.50	100.00	D019675	1.50	0.006		0.006
			100.00	101.50	D019676	1.50	0.005		0.005
			101.50	103.00	D019678	1.50	0.007		0.007
			103.00	104.50	D019679	1.50	0.018		0.018
			104.50	106.00	D019680	1.50	0.028		0.028
			106.00	107.50	D019681	1.50	0.136		0.136
			107.50	109.00	D019682	1.50	0.135		0.135
			109.00	110.50	D019683	1.50	0.049		0.049
			110.50	112.00	D019684	1.50	0.105		0.105
			112.00	113.50	D019685	1.50	0.042		0.042
			113.50	115.00	D019686	1.50	0.034		0.034
			115.00	116.50	D019688	1.50	0.454		0.454
			116.50	118.00	D019689	1.50	0.592		0.592
			118.00	119.50	D019690	1.50	0.030		0.030
			119.50	121.00	D019691	1.50	0.159		0.159
			121.00	122.50	D019692	1.50	0.068		0.068
			122.50	124.00	D019693	1.50	0.100		0.100
124.00	125.50	D019694	1.50	0.008		0.008			
125.50	127.00	D019695	1.50	<0.005		0.001			
127.00	128.50	D019696	1.50	0.013		0.013			
128.50	130.00	D019698	1.50	0.008		0.008			
130.00	131.50	D019699	1.50	0.933		0.933			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	131.50	133.00	D019700	1.50	0.351		0.351
	133.00	134.50	D019701	1.50	0.373		0.373
	134.50	136.00	D019703	1.50	0.205		0.205
	136.00	137.50	D019704	1.50	0.097		0.097
	137.50	139.00	D019705	1.50	0.063		0.063
	139.00	140.50	D019706	1.50	0.018		0.018
	140.50	142.00	D019708	1.50	0.072		0.072
	142.00	143.50	D019709	1.50	0.018		0.018
	143.50	145.00	D019710	1.50	0.017		0.017
	145.00	146.50	D019711	1.50	0.064		0.064
	146.50	148.00	D019712	1.50	0.039		0.039
	148.00	149.50	D019713	1.50	0.007		0.007
	149.50	151.00	D019714	1.50	0.016		0.016
	151.00	152.50	D019715	1.50	0.063		0.063
	152.50	154.00	D019716	1.50	0.110		0.110
	154.00	155.50	D019718	1.50	0.005		0.005
	155.50	157.00	D019719	1.50	0.018		0.018
	157.00	158.50	D019720	1.50	0.006		0.006
	158.50	160.00	D019721	1.50	0.043		0.043
	160.00	161.50	D019722	1.50	0.029		0.029
	161.50	163.00	D019723	1.50	0.158		0.158
	163.00	164.50	D019724	1.50	0.020		0.020
	164.50	166.00	D019725	1.50	0.007		0.007
	166.00	167.50	D019726	1.50	0.007		0.007
	167.50	169.00	D019728	1.50	0.007		0.007
	169.00	170.50	D019729	1.50	0.006		0.006
	170.50	172.00	D019730	1.50	0.005		0.005
	172.00	173.50	D019731	1.50	0.007		0.007
	173.50	175.00	D019732	1.50	0.005		0.005
	175.00	176.50	D019733	1.50	0.006		0.006
	176.50	178.00	D019734	1.50	0.008		0.008
	178.00	179.50	D019735	1.50	0.015		0.015
	179.50	181.00	D019736	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			181.00	182.50	D019738	1.50		0.012	0.012
			182.50	184.00	D019739	1.50		0.018	0.018
			184.00	185.50	D019740	1.50		0.029	0.029
			185.50	187.00	D019741	1.50		<0.005	0.001
81.90	127.00	CIS <b>Cisaillement</b> Cisaillé à tendance sub-// à ac.							
187.50	279.00	UM; MAS; APH <b>Ultramaïfite serpentinisée 35°; Roche massive; Aphanitique</b> Massive, aphanitique, talqueuse, rayée au couteau, avec VCB irrégulières à régulières et quelque fois sub-bréchifiantes.	187.50	189.00	D019743	1.50		<0.005	0.001
			189.00	190.50	D019744	1.50		<0.005	0.001
			190.50	192.00	D019745	1.50		<0.005	0.001
			192.00	193.50	D019746	1.50		<0.005	0.001
			193.50	195.00	D019748	1.50		<0.005	0.001
			195.00	196.50	D019749	1.50		<0.005	0.001
			196.50	198.00	D019750	1.50		<0.005	0.001
			198.00	199.50	D019751	1.50		<0.005	0.001
			199.50	201.00	D019752	1.50		<0.005	0.001
			201.00	202.50	D019753	1.50		<0.005	0.001
			202.50	204.00	D019754	1.50		<0.005	0.001
			204.00	205.50	D019755	1.50		<0.005	0.001
			205.50	207.00	D019756	1.50		<0.005	0.001
			207.00	208.50	D019758	1.50		<0.005	0.001
			208.50	210.00	D019759	1.50		<0.005	0.001
			210.00	211.50	D019760	1.50		<0.005	0.001
			211.50	213.00	D019761	1.50		<0.005	0.001
			213.00	214.50	D019762	1.50		<0.005	0.001
			214.50	216.00	D019763	1.50		<0.005	0.001
			216.00	217.50	D019764	1.50		<0.005	0.001
			217.50	219.00	D019765	1.50		<0.005	0.001
			219.00	220.50	D019766	1.50		<0.005	0.001
			220.50	222.00	D019768	1.50		<0.005	0.001
			222.00	223.50	D019769	1.50		<0.005	0.001
			223.50	225.00	D019770	1.50		<0.005	0.001
			225.00	226.50	D019771	1.50		<0.005	0.001
			226.50	228.00	D019772	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	228.00	229.50	D019773	1.50	<0.005		0.001
	229.50	231.00	D019774	1.50	<0.005		0.001
	231.00	232.50	D019775	1.50	<0.005		0.001
	232.50	234.00	D019776	1.50	<0.005		0.001
	234.00	235.50	D019778	1.50	<0.005		0.001
	235.50	237.00	D019779	1.50	<0.005		0.001
	237.00	238.50	D019780	1.50	<0.005		0.001
	238.50	240.00	D019781	1.50	<0.005		0.001
	240.00	241.50	D019783	1.50	<0.005		0.001
	241.50	243.00	D019784	1.50	<0.005		0.001
	243.00	244.50	D019785	1.50	<0.005		0.001
	244.50	246.00	D019786	1.50	<0.005		0.001
	246.00	247.50	D019788	1.50	<0.005		0.001
	247.50	249.00	D019789	1.50	<0.005		0.001
	249.00	250.50	D019790	1.50	<0.005		0.001
	250.50	252.00	D019791	1.50	<0.005		0.001
	252.00	253.50	D019792	1.50	<0.005		0.001
	253.50	255.00	D019793	1.50	<0.005		0.001
	255.00	256.50	D019794	1.50	<0.005		0.001
	256.50	258.00	D019795	1.50	0.020		0.020
	258.00	259.50	D019796	1.50	0.025		0.025
	259.50	261.00	D019798	1.50	0.005		0.005
	261.00	262.50	D019799	1.50	0.005		0.005
	262.50	264.00	D019800	1.50	<0.005		0.001
	264.00	265.50	D019801	1.50	<0.005		0.001
	265.50	267.00	D019802	1.50	<0.005		0.001
	267.00	268.50	D019803	1.50	<0.005		0.001
	268.50	270.00	D019804	1.50	<0.005		0.001
	270.00	271.50	D019805	1.50	<0.005		0.001
	271.50	273.00	D019806	1.50	<0.005		0.001
	273.00	274.50	D019808	1.50	<0.005		0.001
	274.50	276.00	D019809	1.50	<0.005		0.001
	276.00	277.50	D019810	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
279.00	281.00	NR <b>Carotte perdue</b> Carotte non récupérée.	277.50	279.00	D019811	1.50	<0.005		0.001
281.00	304.00	UM; MAS; APH <b>Ultramafite serpentinisée; Roche massive; Aphanitique</b> Massive, aphanitique, talqueuse, beaucoup de VCB sans orientation préférentielle, passage de spinifex.	281.00	282.50	D019812	1.50	0.007		0.007
			282.50	284.00	D019813	1.50	<0.005		0.001
			284.00	285.50	D019814	1.50	<0.005		0.001
			285.50	287.00	D019815	1.50	<0.005		0.001
			287.00	288.50	D019816	1.50	<0.005		0.001
			288.50	290.00	D019818	1.50	<0.005		0.001
			290.00	291.50	D019819	1.50	<0.005		0.001
			291.50	293.00	D019820	1.50	0.005		0.005
			293.00	294.50	D019821	1.50	<0.005		0.001
			294.50	296.00	D019823	1.50	<0.005		0.001
			296.00	297.50	D019824	1.50	<0.005		0.001
			297.50	299.00	D019825	1.50	<0.005		0.001
			299.00	300.50	D019826	1.50	<0.005		0.001
			300.50	302.00	D019828	1.50	<0.005		0.001
			302.00	303.00	D019829	1.00	<0.005		0.001
			303.00	304.00	D019830	1.00	<0.005		0.001
304.00	338.00	GR; MAS; FIN; MTY <b>Grès 40°; Roche massive; Grains fins; Grains moyens</b> Massive, grains fins à grains moyens, passage bréchifié à matrice graphiteuse et cisailé.	304.00	305.50	D019831	1.50	0.006		0.006
			305.50	307.00	D019832	1.50	<0.005		0.001
			307.00	308.50	D019833	1.50	<0.005		0.001
			308.50	310.00	D019834	1.50	<0.005		0.001
			310.00	311.50	D019835	1.50	<0.005		0.001
			311.50	313.00	D019836	1.50	<0.005		0.001
			313.00	314.50	D019838	1.50	<0.005		0.001
			314.50	316.00	D019839	1.50	<0.005		0.001
			316.00	317.50	D019840	1.50	<0.005		0.001
			317.50	319.00	D019841	1.50	<0.005		0.001
			319.00	320.50	D019842	1.50	<0.005		0.001
			320.50	322.00	D019843	1.50	<0.005		0.001
			322.00	323.50	D019844	1.50	<0.005		0.001
			323.50	325.00	D019845	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	325.00	326.50	D019846	1.50	<0.005		0.001
	326.50	328.00	D019848	1.50	<0.005		0.001
	328.00	329.50	D019849	1.50	<0.005		0.001
	329.50	331.00	D019850	1.50	<0.005		0.001
	331.00	332.50	D019851	1.50	<0.005		0.001
	332.50	334.00	D019852	1.50	<0.005		0.001
	334.00	335.50	D019853	1.50	<0.005		0.001
	335.50	337.00	D019854	1.50	<0.005		0.001
	337.00	338.00	D019855	1.00	<0.005		0.001
338.00	Fin du sondage Nombre d'échantillons : 199 Nombre d'échantillons QAQC : 27 Longueur totale échantillonnée : 296.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
47.00	48.50	D019637	D019636	1.50	0.008	0.008
60.50	60.50	D019647	M	0.00	3.060	3.060
74.00	75.50	D019657	D019656	1.50	0.062	0.062
80.00	80.00	D019662	M1	0.00	<0.005	0.001
86.50	86.50	D019667	J	0.00	0.788	0.788
100.00	101.50	D019677	D019676	1.50	<0.005	0.001
113.50	113.50	D019687	K	0.00	1.045	1.045
127.00	128.50	D019697	D019696	1.50	0.010	0.010
133.00	133.00	D019702	M1	0.00	0.006	0.006
139.00	139.00	D019707	L	0.00	2.290	2.290
152.50	154.00	D019717	D019716	1.50	0.042	0.042
166.00	166.00	D019727	M	0.00	3.170	3.170
179.50	181.00	D019737	D019736	1.50	0.009	0.009
185.50	185.50	D019742	M1	0.00	<0.005	0.001
192.00	192.00	D019747	J	0.00	0.816	0.816
205.50	207.00	D019757	D019756	1.50	<0.005	0.001
219.00	219.00	D019767	K	0.00	0.996	0.996
232.50	234.00	D019777	D019776	1.50	<0.005	0.001
238.50	238.50	D019782	M1	0.00	<0.005	0.001
244.50	244.50	D019787	L	0.00	2.200	2.200
258.00	259.50	D019797	D019796	1.50	0.022	0.022
271.50	271.50	D019807	M	0.00	3.040	3.040
287.00	288.50	D019817	D019816	1.50	<0.005	0.001
293.00	293.00	D019822	M1	0.00	<0.005	0.001
299.00	299.00	D019827	J	0.00	0.838	0.838
311.50	313.00	D019837	D019836	1.50	<0.005	0.001
325.00	325.00	D019847	K	0.00	1.035	1.035



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	31.00	MT						
		<b>Mort-terrain</b>						
31.00	68.00	TU; FIN; LAM	31.00	32.50	D002692	1.50	0.016	0.016
		<b>Tuf à cendre/lapillis; Grains fins; Laminations parallèles</b>	32.50	34.00	D002693	1.50	0.030	0.030
		rubané, schisteuse, folié et plissé, alternance de lits cm séricitisés et chloritisés intercalations de sédiments. Veines, veinules de QZ et carbonâtes cm, lamines de talc, jaspe, SR++, CL+++, PY fine irrég diss						
33.50	33.80	FRC	34.00	35.50	D002694	1.50	0.076	0.076
		<b>Fracturé 40°</b>						
		fragments mêlés cm						
34.50	35.00	FRC	35.50	37.00	D002695	1.50	0.007	0.007
		<b>Fracturé</b>						
36.00	36.50	FRC	37.00	38.50	D002696	1.50	0.016	0.016
		<b>Fracturé</b>	38.50	40.00	D002697	1.50	0.049	0.049
		fragments mm- cm	40.00	41.50	D002698	1.50	0.076	0.076
			41.50	43.00	D002699	1.50	0.056	0.056
			43.00	44.50	D002700	1.50	0.008	0.008
			44.50	46.00	D002702	1.50	0.173	0.173
			46.00	47.50	D002703	1.50	0.218	0.218
			47.50	49.00	D002704	1.50	0.027	0.027
47.80	62.00	FRC	49.00	50.50	D002705	1.50	0.014	0.014
		<b>Fracturé</b>	50.50	52.00	D002706	1.50	<0.005	0.001
		zone de faille avec fragments mêlés et boue verdâtre	52.00	53.50	D002707	1.50	<0.005	0.001
			53.50	55.00	D002708	1.50	0.005	0.005
			55.00	56.50	D002709	1.50	0.024	0.024
			56.50	58.00	D002710	1.50	0.087	0.087
			58.00	59.50	D002712	1.50	0.207	0.207
			59.50	61.00	D002713	1.50	0.212	0.212
			61.00	62.50	D002714	1.50	0.008	0.008
			62.50	64.00	D002715	1.50	0.018	0.018
			64.00	65.50	D002716	1.50	0.135	0.135
			65.50	67.00	D002717	1.50	0.041	0.041
			67.00	68.00	D002718	1.00	0.125	0.125
68.00	89.30	GR; MAS; FIN	68.00	69.50	D002719	1.50	0.011	0.011
		<b>Grès; Roche massive; Grains fins</b>	69.50	71.00	D002720	1.50	0.008	0.008

Corporation Minière Osisko Div. Exploration

Description				Analyse					
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
80.00	82.60	FRC <b>Fracturé 60°</b>	71.00	72.50	D002722	1.50	0.017		0.017
			72.50	74.00	D002723	1.50	0.006		0.006
			74.00	75.50	D002724	1.50	0.009		0.009
			75.50	77.00	D002725	1.50	0.005		0.005
			77.00	78.50	D002726	1.50	0.006		0.006
			78.50	80.00	D002727	1.50	<0.005		0.001
			80.00	81.50	D002729	1.50	<0.005		0.001
			81.50	83.00	D002730	1.50	<0.005		0.001
			83.00	84.50	D002732	1.50	0.005		0.005
			84.50	86.00	D002733	1.50	<0.005		0.001
			86.00	87.30	D002734	1.30	0.021		0.021
			87.30	88.30	D002735	1.00	<0.005		0.001
			88.30	89.30	D002736	1.00	0.006		0.006
			89.30	102.40	TU; FIN; LAM; RUB <b>Tuf à cendre/lapillis; Grains fins; Laminations parallèles; Rubané</b>	89.30	90.50	D002737	1.20
90.50	92.00	D002738				1.50	0.035		0.035
92.00	93.50	D002739				1.50	0.060		0.060
93.50	95.00	D002740				1.50	0.015		0.015
95.00	96.50	D002742				1.50	0.066		0.066
96.50	98.00	D002743				1.50	0.029		0.029
98.00	99.50	D002744				1.50	0.054		0.054
99.50	101.00	D002745				1.50	0.033		0.033
101.00	102.40	D002746				1.40	0.011		0.011
102.40	119.00	GR; MAS; FIN; MTY <b>Grès 70°; Roche massive; Grains fins; Grains moyens</b>				102.40	104.00	D002747	1.60
			104.00	105.50	D002748	1.50	0.007		0.007
			105.50	107.00	D002749	1.50	0.009		0.009
			107.00	108.50	D002750	1.50	0.006		0.006
			108.50	110.00	D002752	1.50	<0.005		0.001
			110.00	111.50	D002753	1.50	0.005		0.005
			111.50	113.00	D002754	1.50	<0.005		0.001
			113.00	114.50	D002755	1.50	0.006		0.006
			114.50	116.00	D002756	1.50	0.009		0.009
			116.00	117.50	D002757	1.50	0.012		0.012
117.50	119.00	D002758	1.50	0.008		0.008			
117.50	136.40	CIS							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Cisaillement 40°</b> cisaillement avec fragments cm entre 133.50-1340 m						
119.00	136.40	TU; RUB; LAM	119.00	120.50	D002759	1.50	0.008	0.008
		<b>Tuf à cendre/lapillis 70°; Rubané; Laminations parallèles</b>	120.50	122.00	D002760	1.50	0.005	0.005
		foliation et schistosité 60-80° ac, veinules et cheveux de QZ et	122.00	123.50	D002762	1.50	<0.005	0.001
		carbonâtes // schistosité, lamines de talc, SR+++ , CL++ , localement	123.50	125.00	D002763	1.50	0.005	0.005
		fragmenté	125.00	126.50	D002764	1.50	0.006	0.006
			126.50	128.00	D002765	1.50	0.006	0.006
			128.00	129.50	D002766	1.50	<0.005	0.001
			129.50	131.00	D002767	1.50	0.007	0.007
			131.00	132.50	D002769	1.50	0.016	0.016
			132.50	134.00	D002770	1.50	0.048	0.048
			134.00	135.30	D002772	1.30	0.103	0.103
			135.30	136.40	D002773	1.10	0.136	0.136
136.40	148.30	GR; MAS; MTY; MOY; FIN	136.40	138.00	D002774	1.60	0.010	0.010
		<b>Grès 40°; Roche massive; Grains moyens; Grains</b>	138.00	139.50	D002775	1.50	0.007	0.007
		<b>moyens; Grains fins</b>	139.50	141.00	D002776	1.50	<0.005	0.001
		altération en séricite et légère chloritisation, localement laminations à	141.00	142.00	D002777	1.00	0.005	0.005
		grains très fin, lentilles de QZ , veines et veinules de QZ 1-10 cm, PY	142.00	143.00	D002778	1.00	0.005	0.005
		fine diss	143.00	144.50	D002779	1.50	0.010	0.010
			144.50	146.00	D002780	1.50	0.038	0.038
			146.00	147.00	D002782	1.00	0.010	0.010
			147.00	148.30	D002783	1.30	0.047	0.047
148.30	170.00	TU; TU; RUB	148.30	149.50	D002784	1.20	0.005	0.005
		<b>Tuf à cendre/lapillis 50°; Tuf à cendre/lapillis; Rubané</b>						
		folié et légèrement schisteuse 40-60° ac, localement cisailé 40-50° ac,						
		alternance de lit à QZ et carbonâtes et des lits séricitisé chloritisé						
		et/ou biotisé, laminations, hématisation, altération potassique, CL++ , PY						
		fine diss						
149.00	156.80	CIS	149.50	150.80	D002785	1.30	<0.005	0.001
		<b>Cisaillement 50°</b>						
150.80	156.80	TU; POR; RUB; RUB	150.80	152.00	D002786	1.20	0.010	0.010
		<b>Tuf à cristaux felsique 50°; Porphyrique; Rubané;</b>	152.00	153.50	D002787	1.50	<0.005	0.001
		<b>Rubané</b>	153.50	155.00	D002788	1.50	<0.005	0.001
		tuf schisteux et folié 40-50° ac, cristaux de QZ et FP mm sub	155.00	156.00	D002789	1.00	<0.005	0.001
		arrondi orienté( trachytique) 40-50° ac, alternance de lits						

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
carbonatés et séricitisés et chloritisé, EP++, HM++, altération potassique, PY fine irrég diss	156.00	156.80	D002790	0.80	<0.005		0.001
	156.80	158.00	D002792	1.20	<0.005		0.001
	158.00	159.40	D002793	1.40	<0.005		0.001
	159.40	161.00	D002794	1.60	<0.005		0.001
	161.00	162.50	D002795	1.50	<0.005		0.001
	162.50	164.00	D002796	1.50	<0.005		0.001
	164.00	165.70	D002797	1.70	<0.005		0.001
	165.70	167.00	D002798	1.30	<0.005		0.001
	167.00	168.50	D002799	1.50	<0.005		0.001
	168.50	170.00	D002800	1.50	<0.005		0.001
170.00	Fin du sondage Nombre d'échantillons : 97 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 139.00						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
43.00	44.50	D002701	D002700	1.50	0.008	0.008
56.50	58.00	D002711	A3	1.50	0.584	0.584
69.50	71.00	D002721	D002720	1.50	0.006	0.006
78.50	80.00	D002728	M1	1.50	<0.005	0.001
81.50	83.00	D002731	B4	1.50	2.600	2.600
93.50	95.00	D002741	D002740	1.50	0.045	0.045
107.00	107.00	D002751	C4	0.00	1.090	1.090
120.50	122.00	D002761	D002760	1.50	0.006	0.006
129.50	131.00	D002768	M1	1.50	<0.005	0.001
132.50	134.00	D002771	D2	1.50	0.857	0.857
144.50	146.00	D002781	D002780	1.50	0.108	0.108
156.00	156.00	D002791	F2	0.00	8.420	8.440

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-166**

Titre minier :

Section :                      631200

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          Guy Gbaguidi

Du :                      2010-04-14

Date de description :

Au :                      2010-04-18

Collet

UTM

Azimut :                0.00°  
 Plongée :              -60.00°  
 Longueur :            467.00 m

Est	631 200.3
Nord	5 374 352.0
Élévation	306.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	159.00°	-60.00°	Oui
Reflex	8.00	0.60°	-59.60°	Non
Reflex	11.00	359.50°	-59.40°	Non
Reflex	14.00	359.10°	-59.30°	Non
Reflex	17.00	359.20°	-59.20°	Non
Reflex	20.00	359.10°	-59.20°	Non
Reflex	23.00	359.00°	-59.10°	Non
Reflex	26.00	358.90°	-59.00°	Non
Reflex	29.00	358.90°	-59.00°	Non
Reflex	32.00	358.80°	-59.00°	Non
Reflex	35.00	358.70°	-58.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.70°	-58.80°	Non
Reflex	41.00	358.80°	-58.80°	Non
Reflex	44.00	358.70°	-58.80°	Non
Reflex	47.00	358.80°	-58.80°	Non
Reflex	50.00	358.80°	-58.70°	Non
Reflex	53.00	358.90°	-58.70°	Non
Reflex	56.00	358.80°	-58.70°	Non
Reflex	59.00	358.80°	-58.70°	Non
Reflex	62.00	358.90°	-58.70°	Non
Reflex	65.00	358.70°	-58.70°	Non
Reflex	68.00	358.90°	-58.60°	Non
Reflex	71.00	355.20°	-58.60°	Oui

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	5.00	MT						
		<b>Mort-terrain</b>						
5.00	467.00	SY; POR	5.00	6.40	D013504	1.40	0.176	0.176
		<b>Syénite; Porphyrique</b>						
		Porphyre syénitique carbonaté, hématisé et séricitisé, localement magnétique, parfois silicifié.	6.40	8.00	D013506	1.60	0.061	0.061
			8.00	9.50	D013507	1.50	<0.005	0.001
			9.50	11.00	D013508	1.50	0.089	0.089
			11.00	12.50	D013509	1.50	0.098	0.098
			12.50	14.00	D013510	1.50	0.461	0.461
			14.00	15.50	D013511	1.50	0.009	0.009
			15.50	17.00	D013512	1.50	0.041	0.041
			17.00	18.50	D013513	1.50	0.009	0.009
			18.50	20.00	D013514	1.50	0.067	0.067
			20.00	21.50	D013516	1.50	0.012	0.012
			21.50	23.00	D013517	1.50	<0.005	0.001
			23.00	24.50	D013518	1.50	0.007	0.007
			24.50	26.00	D013519	1.50	0.607	0.607
			26.00	27.50	D013521	1.50	0.147	0.147
			27.50	29.00	D013522	1.50	0.157	0.157
			29.00	30.50	D013523	1.50	0.084	0.084
			30.50	32.00	D013524	1.50	0.011	0.011
			32.00	33.50	D013526	1.50	0.028	0.028
			33.50	35.00	D013527	1.50	0.061	0.061
			35.00	36.50	D013528	1.50	0.070	0.070
			36.50	38.00	D013529	1.50	0.044	0.044
			38.00	39.50	D013530	1.50	0.150	0.150
			39.50	41.00	D013531	1.50	0.128	0.128
			41.00	42.50	D013532	1.50	0.043	0.043
			42.50	44.00	D013533	1.50	0.007	0.007
			44.00	45.50	D013534	1.50	0.040	0.040
			45.50	47.00	D013536	1.50	0.105	0.105
			47.00	48.50	D013537	1.50	0.769	0.769
			48.50	50.00	D013538	1.50	0.011	0.011
			50.00	51.50	D013539	1.50	0.016	0.016
			51.50	53.00	D013540	1.50	0.032	0.032

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	53.00	54.50	D013541	1.50	0.023		0.023
	54.50	56.00	D013542	1.50	0.029		0.029
	56.00	57.50	D013543	1.50	0.096		0.096
	57.50	59.00	D013544	1.50	0.030		0.030
	59.00	60.50	D013546	1.50	0.051		0.051
	60.50	62.00	D013547	1.50	0.047		0.047
	62.00	63.50	D013548	1.50	0.040		0.040
	63.50	65.00	D013549	1.50	0.074		0.074
	65.00	66.50	D013550	1.50	0.013		0.013
	66.50	68.00	D013551	1.50	0.012		0.012
	68.00	69.50	D013552	1.50	0.129		0.129
	69.50	71.00	D013553	1.50	1.160		1.160
	71.00	72.50	D013554	1.50	0.448		0.448
	72.50	74.00	D013556	1.50	0.012		0.012
	74.00	75.00	D013557	1.00	0.312		0.312
	75.00	76.00	D013558	1.00	0.264		0.264
	76.00	77.00	D013559	1.00	1.620		1.620
	77.00	78.30	D013561	1.30	1.835		1.835
	78.30	80.00	D013562	1.70	0.023		0.023
	80.00	81.50	D013563	1.50	0.141		0.141
	81.50	83.00	D013564	1.50	0.009		0.009
	83.00	84.50	D013566	1.50	<0.005		0.001
	84.50	86.00	D013567	1.50	0.043		0.043
	86.00	87.50	D013568	1.50	0.023		0.023
	87.50	89.00	D013569	1.50	0.265		0.265
	89.00	90.50	D013570	1.50	0.136		0.136
	90.50	92.00	D013571	1.50	<0.005		0.001
	92.00	93.50	D013572	1.50	<0.005		0.001
	93.50	95.00	D013573	1.50	<0.005		0.001
	95.00	96.50	D013574	1.50	0.005		0.005
	96.50	98.00	D013576	1.50	<0.005		0.001
	98.00	99.50	D013577	1.50	0.007		0.007
	99.50	101.00	D013578	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	101.00	102.50	D013579	1.50	<0.005		0.001
	102.50	104.00	D013580	1.50	0.006		0.006
	104.00	105.50	D013581	1.50	0.144		0.144
	105.50	107.00	D013582	1.50	<0.005		0.001
	107.00	108.50	D013583	1.50	0.043		0.043
	108.50	110.00	D013584	1.50	<0.005		0.001
	110.00	111.50	D013586	1.50	0.007		0.007
	111.50	113.00	D013587	1.50	0.006		0.006
	113.00	114.50	D013588	1.50	0.075		0.075
	114.50	116.00	D013589	1.50	0.044		0.044
	116.00	117.50	D013590	1.50	0.133		0.133
	117.50	119.00	D013591	1.50	0.006		0.006
	119.00	120.50	D013592	1.50	<0.005		0.001
	120.50	122.00	D013593	1.50	<0.005		0.001
	122.00	123.50	D013594	1.50	0.075		0.075
	123.50	125.00	D013596	1.50	0.005		0.005
	125.00	126.50	D013597	1.50	0.006		0.006
	126.50	128.00	D013598	1.50	0.019		0.019
	128.00	129.50	D013599	1.50	0.018		0.018
	129.50	130.50	D013601	1.00	0.007		0.007
	130.50	131.80	D013602	1.30	0.022		0.022
	131.80	133.30	D013603	1.50	0.940		0.940
	133.30	135.00	D013604	1.70	0.014		0.014
	135.00	136.50	D013606	1.50	0.027		0.027
	136.50	138.00	D013607	1.50	<0.005		0.001
	138.00	139.50	D013608	1.50	<0.005		0.001
	139.50	141.00	D013609	1.50	0.023		0.023
	141.00	142.50	D013610	1.50	0.087		0.087
	142.50	144.00	D013611	1.50	0.019		0.019
	144.00	145.50	D013612	1.50	<0.005		0.001
	145.50	147.00	D013613	1.50	<0.005		0.001
	147.00	148.50	D013614	1.50	<0.005		0.001
	148.50	150.00	D013616	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	150.00	151.50	D013617	1.50	<0.005		0.001
	151.50	153.00	D013618	1.50	0.010		0.010
	153.00	154.50	D013619	1.50	0.152		0.152
	154.50	156.00	D013620	1.50	0.181		0.181
	156.00	157.20	D013621	1.20	0.006		0.006
	157.20	158.90	D013622	1.70	0.007		0.007
	158.90	160.50	D013623	1.60	<0.005		0.001
	160.50	162.00	D013624	1.50	<0.005		0.001
	162.00	163.50	D013626	1.50	<0.005		0.001
	163.50	165.00	D013627	1.50	0.125		0.125
	165.00	166.50	D013628	1.50	<0.005		0.001
	166.50	168.00	D013629	1.50	<0.005		0.001
	168.00	169.50	D013630	1.50	<0.005		0.001
	169.50	171.00	D013631	1.50	<0.005		0.001
	171.00	172.50	D013632	1.50	0.006		0.006
	172.50	174.00	D013633	1.50	<0.005		0.001
	174.00	175.50	D013634	1.50	<0.005		0.001
	175.50	177.00	D013636	1.50	<0.005		0.001
	177.00	178.50	D013637	1.50	0.021		0.021
	178.50	180.00	D013638	1.50	<0.005		0.001
	180.00	181.50	D013639	1.50	0.020		0.020
	181.50	183.00	D013641	1.50	0.018		0.018
	183.00	184.50	D013642	1.50	0.118		0.118
	184.50	186.00	D013643	1.50	<0.005		0.001
	186.00	187.50	D013644	1.50	<0.005		0.001
	187.50	189.00	D013646	1.50	<0.005		0.001
	189.00	190.50	D013647	1.50	0.016		0.016
	190.50	192.00	D013648	1.50	0.009		0.009
	192.00	193.50	D013649	1.50	0.010		0.010
	193.50	195.00	D013650	1.50	<0.005		0.001
	195.00	196.50	D013651	1.50	0.016		0.016
	196.50	198.00	D013652	1.50	0.030		0.030
	198.00	199.00	D013653	1.00	0.068		0.068

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	199.00	200.10	D013654	1.10	2.680		2.680
	200.10	201.80	D013656	1.70	0.012		0.012
	201.80	203.50	D013657	1.70	0.031		0.031
	203.50	205.00	D013658	1.50	0.188		0.188
	205.00	206.50	D013659	1.50	0.007		0.007
	206.50	208.00	D013660	1.50	0.015		0.015
	208.00	209.50	D013661	1.50	<0.005		0.001
	209.50	211.00	D013662	1.50	0.020		0.020
	211.00	212.50	D013663	1.50	0.007		0.007
	212.50	214.00	D013664	1.50	<0.005		0.001
	214.00	215.50	D013666	1.50	<0.005		0.001
	215.50	217.00	D013667	1.50	0.019		0.019
	217.00	218.50	D013668	1.50	<0.005		0.001
	218.50	220.00	D013669	1.50	<0.005		0.001
	220.00	221.00	D013670	1.00	0.005		0.005
	221.00	222.50	D013671	1.50	0.212		0.212
	222.50	224.00	D013672	1.50	<0.005		0.001
	224.00	225.50	D013673	1.50	<0.005		0.001
	225.50	227.00	D013674	1.50	0.012		0.012
	227.00	228.50	D013676	1.50	0.007		0.007
	228.50	230.00	D013677	1.50	0.007		0.007
	230.00	231.50	D013678	1.50	0.048		0.048
	231.50	233.00	D013679	1.50	0.119		0.119
	233.00	234.50	D013681	1.50	0.006		0.006
	234.50	236.00	D013682	1.50	0.008		0.008
	236.00	237.50	D013683	1.50	0.005		0.005
	237.50	238.80	D013684	1.30	0.026		0.026
	238.80	240.00	D013686	1.20	0.599		0.599
	240.00	241.50	D013687	1.50	0.044		0.044
	241.50	243.00	D013688	1.50	0.095		0.095
	243.00	244.50	D013689	1.50	0.039		0.039
	244.50	246.00	D013690	1.50	0.041		0.041
	246.00	247.50	D013691	1.50	0.168		0.168

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	247.50	249.00	D013692	1.50	0.032		0.032
	249.00	250.50	D013693	1.50	0.007		0.007
	250.50	252.00	D013694	1.50	0.016		0.016
	252.00	253.50	D013696	1.50	0.007		0.007
	253.50	255.00	D013697	1.50	0.013		0.013
	255.00	256.50	D013698	1.50	0.014		0.014
	256.50	258.00	D013699	1.50	0.018		0.018
	258.00	259.50	D013700	1.50	0.028		0.028
	259.50	261.00	D013701	1.50	0.006		0.006
	261.00	262.50	D013702	1.50	<0.005		0.001
	262.50	264.00	D013703	1.50	1.120		1.120
	264.00	265.50	D013704	1.50	<0.005		0.001
	265.50	267.00	D013706	1.50	0.029		0.029
	267.00	268.50	D013707	1.50	0.873		0.873
	268.50	270.00	D013708	1.50	0.065		0.065
	270.00	271.50	D013709	1.50	0.098		0.098
	271.50	273.00	D013710	1.50	0.277		0.277
	273.00	274.50	D013711	1.50	0.194		0.194
	274.50	276.00	D013712	1.50	0.402		0.402
	276.00	277.30	D013713	1.30	0.085		0.085
	277.30	279.00	D013714	1.70	0.022		0.022
	279.00	280.50	D013716	1.50	<0.005		0.001
	280.50	282.00	D013717	1.50	0.006		0.006
	282.00	283.50	D013718	1.50	0.050		0.050
	283.50	285.00	D013719	1.50	0.042		0.042
	285.00	286.50	D013721	1.50	0.196		0.196
	286.50	288.00	D013722	1.50	0.431		0.431
	288.00	289.50	D013723	1.50	0.006		0.006
	289.50	291.00	D013724	1.50	0.015		0.015
	291.00	292.50	D013726	1.50	0.126		0.126
	292.50	294.00	D013727	1.50	0.024		0.024
	294.00	295.50	D013728	1.50	0.006		0.006
	295.50	297.00	D013729	1.50	0.010		0.010



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	297.00	298.50	D013730	1.50	0.014		0.014
	298.50	300.00	D013731	1.50	0.016		0.016
	300.00	301.50	D013732	1.50	0.007		0.007
	301.50	303.00	D013733	1.50	0.414		0.414
	303.00	304.50	D013734	1.50	0.461		0.461
	304.50	306.00	D013736	1.50	0.006		0.006
	306.00	307.50	D013737	1.50	0.021		0.021
	307.50	309.00	D013738	1.50	<0.005		0.001
	309.00	310.50	D013739	1.50	0.011		0.011
	310.50	312.00	D013740	1.50	0.017		0.017
	312.00	313.50	D013741	1.50	0.015		0.015
	313.50	315.00	D013742	1.50	0.010		0.010
	315.00	316.50	D013743	1.50	0.199		0.199
	316.50	318.00	D013744	1.50	1.770		1.770
	318.00	319.50	D013746	1.50	0.357		0.357
	319.50	321.00	D013747	1.50	0.014		0.014
	321.00	322.50	D013748	1.50	0.361		0.361
	322.50	324.00	D013749	1.50	<0.005		0.001
	324.00	325.50	D013750	1.50	0.157		0.157
	325.50	327.00	D013751	1.50	0.092		0.092
	327.00	328.50	D013752	1.50	0.016		0.016
	328.50	330.00	D013753	1.50	0.013		0.013
	330.00	331.50	D013754	1.50	<0.005		0.001
	331.50	333.00	D013756	1.50	0.005		0.005
	333.00	334.50	D013757	1.50	0.010		0.010
	334.50	336.00	D013758	1.50	0.062		0.062
	336.00	337.50	D013759	1.50	0.179		0.179
	337.50	339.00	D013761	1.50	0.122		0.122
	339.00	340.50	D013762	1.50	0.010		0.010
	340.50	342.00	D013763	1.50	0.013		0.013
	342.00	343.50	D013764	1.50	0.005		0.005
	343.50	345.00	D013766	1.50	0.024		0.024
	345.00	346.50	D013767	1.50	0.418		0.418

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	346.50	348.00	D013768	1.50	0.019		0.019
	348.00	349.50	D013769	1.50	0.111		0.111
	349.50	351.00	D013770	1.50	0.050		0.050
	351.00	352.50	D013771	1.50	<0.005		0.001
	352.50	354.00	D013772	1.50	<0.005		0.001
	354.00	355.50	D013773	1.50	0.040		0.040
	355.50	357.00	D013774	1.50	0.069		0.069
	357.00	358.50	D013776	1.50	0.043		0.043
	358.50	360.00	D013777	1.50	0.286		0.286
	360.00	361.50	D013778	1.50	0.701		0.701
	361.50	363.00	D013779	1.50	0.289		0.289
	363.00	364.50	D013780	1.50	0.154		0.154
	364.50	366.00	D013781	1.50	0.028		0.028
	366.00	367.50	D013782	1.50	0.030		0.030
	367.50	369.00	D013783	1.50	0.084		0.084
	369.00	370.50	D013784	1.50	0.108		0.108
	370.50	372.00	D013786	1.50	0.093		0.093
	372.00	373.50	D013787	1.50	0.239		0.239
	373.50	375.00	D013788	1.50	<0.005		0.001
	375.00	376.50	D013789	1.50	0.438		0.438
	376.50	378.00	D013790	1.50	0.067		0.067
	378.00	379.50	D013791	1.50	0.066		0.066
	379.50	381.00	D013792	1.50	0.146		0.146
	381.00	382.50	D013793	1.50	0.281		0.281
	382.50	384.00	D013794	1.50	0.068		0.068
	384.00	385.50	D013796	1.50	0.028		0.028
	385.50	387.00	D013797	1.50	0.254		0.254
	387.00	388.50	D013798	1.50	0.014		0.014
	388.50	390.00	D013799	1.50	<0.005		0.001
	390.00	391.50	D013801	1.50	0.232		0.232
	391.50	393.00	D013802	1.50	0.143		0.143
	393.00	394.50	D013803	1.50	0.009		0.009
	394.50	396.00	D013804	1.50	0.027		0.027

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	396.00	397.50	D013806	1.50	0.129		0.129
	397.50	399.00	D013807	1.50	0.226		0.226
	399.00	400.70	D013808	1.70	1.700		1.700
	400.70	402.00	D013809	1.30	0.013		0.013
	402.00	403.50	D013810	1.50	0.480		0.480
	403.50	405.00	D013811	1.50	0.135		0.135
	405.00	406.50	D013812	1.50	0.179		0.179
	406.50	408.00	D013813	1.50	0.005		0.005
	408.00	409.50	D013814	1.50	<0.005		0.001
	409.50	411.00	D013816	1.50	<0.005		0.001
	411.00	412.50	D013817	1.50	<0.005		0.001
	412.50	414.00	D013818	1.50	<0.005		0.001
	414.00	415.50	D013819	1.50	0.171		0.171
	415.50	417.00	D013820	1.50	<0.005		0.001
	417.00	418.50	D013821	1.50	<0.005		0.001
	418.50	420.00	D013822	1.50	0.006		0.006
	420.00	421.50	D013823	1.50	0.005		0.005
	421.50	423.00	D013824	1.50	<0.005		0.001
	423.00	424.50	D013826	1.50	<0.005		0.001
	424.50	426.00	D013827	1.50	<0.005		0.001
	426.00	427.00	D013828	1.00	<0.005		0.001
	427.00	428.50	D013829	1.50	0.012		0.012
	428.50	430.00	D013830	1.50	0.095		0.095
	430.00	431.50	D013831	1.50	0.008		0.008
	431.50	433.00	D013832	1.50	<0.005		0.001
	433.00	434.50	D013833	1.50	<0.005		0.001
	434.50	436.00	D013834	1.50	0.814		0.814
	436.00	437.50	D013836	1.50	2.910		2.910
	437.50	439.00	D013837	1.50	0.017		0.017
	439.00	440.50	D013838	1.50	0.010		0.010
	440.50	442.00	D013839	1.50	0.017		0.017
	442.00	443.50	D013841	1.50	0.006		0.006
	443.50	445.00	D013842	1.50	1.240		1.240

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	445.00	446.50	D013843	1.50	0.120		0.120
	446.50	448.00	D013844	1.50	0.029		0.029
	448.00	449.50	D013846	1.50	0.005		0.005
	449.50	451.00	D013847	1.50	<0.005		0.001
	451.00	452.50	D013848	1.50	0.005		0.005
	452.50	454.00	D013849	1.50	0.031		0.031
	454.00	455.50	D013850	1.50	0.047		0.047
	455.50	457.00	D013851	1.50	0.008		0.008
	457.00	458.00	D013852	1.00	0.005		0.005
	458.00	459.50	D013853	1.50	0.111		0.111
	459.50	461.00	D013854	1.50	0.196		0.196
	461.00	462.50	D013856	1.50	0.112		0.112
	462.50	464.00	D013857	1.50	0.206		0.206
	464.00	465.50	D013858	1.50	0.890		0.890
	465.50	467.00	D013859	1.50	0.074		0.074
467.00	Fin du sondage Nombre d'échantillons : 311 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 462.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.00	6.40	D013505	D013504	1.40	0.163	0.163
18.50	18.50	D013515	D2	0.00	0.822	0.822
24.50	24.50	D013520	M1	0.00	<0.005	0.001
30.50	32.00	D013525	D013524	1.50	0.016	0.016
44.00	44.00	D013535	F2	0.00	8.260	8.260
57.50	59.00	D013545	D013544	1.50	0.022	0.022
71.00	71.00	D013555	H	0.00	1.005	1.005
76.00	76.00	D013560	M1	0.00	<0.005	0.001
81.50	83.00	D013565	D013564	1.50	0.005	0.005
95.00	95.00	D013575	A3	0.00	0.602	0.602
108.50	110.00	D013585	D013584	1.50	<0.005	0.001
122.00	122.00	D013595	B4	0.00	2.720	2.720
128.00	128.00	D013600	M1	0.00	<0.005	0.001
133.30	135.00	D013605	D013604	1.70	0.026	0.026
147.00	147.00	D013615	C4	0.00	1.330	1.330
160.50	162.00	D013625	D013624	1.50	0.006	0.006
174.00	174.00	D013635	D2	0.00	0.846	0.846
180.00	180.00	D013640	M1	0.00	<0.005	0.001
186.00	187.50	D013645	D013644	1.50	<0.005	0.001
199.00	199.00	D013655	F2	0.00	8.320	8.320
212.50	214.00	D013665	D013664	1.50	0.007	0.007
225.50	225.50	D013675	H	0.00	1.000	1.000
231.50	231.50	D013680	M1	0.00	<0.005	0.001
237.50	238.80	D013685	D013684	1.30	0.034	0.034
250.50	250.50	D013695	A3	0.00	0.645	0.645
264.00	265.50	D013705	D013704	1.50	0.006	0.006
277.30	277.30	D013715	B4	0.00	2.710	2.710
283.50	283.50	D013720	M1	0.00	<0.005	0.001
289.50	291.00	D013725	D013724	1.50	0.015	0.015
303.00	303.00	D013735	C4	0.00	1.365	1.365
316.50	318.00	D013745	D013744	1.50	2.310	2.310
330.00	330.00	D013755	D2	0.00	0.858	0.858
336.00	336.00	D013760	M1	0.00	0.009	0.009

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
342.00	343.50	D013765	D013764	1.50	<0.005	0.001
355.50	355.50	D013775	F2	0.00	8.540	8.540
369.00	370.50	D013785	D013784	1.50	0.126	0.126
382.50	382.50	D013795	H	0.00	0.936	0.936
388.50	388.50	D013800	M1	0.00	<0.005	0.001
394.50	396.00	D013805	D013804	1.50	0.019	0.019
408.00	408.00	D013815	A3	0.00	0.609	0.609
421.50	423.00	D013825	D013824	1.50	0.006	0.006
434.50	434.50	D013835	B4	0.00	2.640	2.640
440.50	440.50	D013840	M1	0.00	<0.005	0.001
446.50	448.00	D013845	D013844	1.50	0.055	0.055
459.50	459.50	D013855	C4	0.00	1.395	1.395

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-167**

Titre minier :

Section :                      630600

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-15

Date de description :

Au :                     2010-04-20

Collet

UTM

Azimut :                0.00°

Plongée :              -60.00°

Longueur :            317.00 m

Est                      630 600.1

Nord                    5 374 451.3

Élévation             303.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	0.00°	0.00°	Oui
Reflex	11.00	0.40°	-57.00°	Non
Reflex	14.00	1.00°	-57.00°	Non
Reflex	17.00	1.10°	-57.00°	Non
Reflex	20.00	1.50°	-57.10°	Non
Reflex	23.00	2.40°	-57.30°	Oui
Reflex	26.00	1.60°	-57.20°	Non
Reflex	29.00	1.70°	-57.30°	Non
Reflex	32.00	2.50°	-57.30°	Non
Reflex	35.00	2.60°	-57.40°	Non
Reflex	38.00	2.50°	-57.30°	Non
Reflex	41.00	1.80°	-57.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	1.60°	-57.50°	Non
Reflex	47.00	1.80°	-57.40°	Non
Reflex	50.00	0.10°	-57.40°	Non
Reflex	53.00	358.20°	-57.40°	Oui
Reflex	56.00	1.50°	-57.40°	Non
Reflex	59.00	1.30°	-57.30°	Non
Reflex	62.00	2.30°	-57.20°	Oui
Reflex	65.00	1.80°	-57.00°	Non
Reflex	68.00	1.70°	-57.00°	Non
Reflex	71.00	1.70°	-57.00°	Non
Reflex	74.00	1.90°	-57.00°	Non
Reflex	77.00	1.80°	-57.00°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	6.50	MT						
		<b>Mort-terrain</b>						
6.50	301.10	SY; FIN; POR; POR	6.50	8.00	D008744	1.50	<0.005	0.001
		<b>Syénite; Grains fins; Porphyrique; Porphyrique</b>	8.00	9.50	D008745	1.50	<0.005	0.001
		Syénite à grains fins et porphyrique avec phénocristaux Xmm à rarement Xcm étalés différentielment (peu à beaucoup).	9.50	11.00	D008746	1.50	<0.005	0.001
			11.00	12.50	D008748	1.50	<0.005	0.001
			12.50	14.00	D008749	1.50	<0.005	0.001
			14.00	15.50	D008750	1.50	<0.005	0.001
			15.50	17.00	D008751	1.50	<0.005	0.001
			17.00	18.50	D008752	1.50	<0.005	0.001
			18.50	20.00	D008753	1.50	<0.005	0.001
			20.00	21.50	D008754	1.50	<0.005	0.001
			21.50	23.00	D008755	1.50	<0.005	0.001
			23.00	24.50	D008756	1.50	0.005	0.005
			24.50	26.00	D008758	1.50	<0.005	0.001
			26.00	27.50	D008759	1.50	<0.005	0.001
			27.50	29.00	D008760	1.50	<0.005	0.001
			29.00	30.50	D008761	1.50	<0.005	0.001
			30.50	32.00	D008762	1.50	<0.005	0.001
			32.00	33.50	D008763	1.50	<0.005	0.001
			33.50	35.00	D008764	1.50	<0.005	0.001
			35.00	36.50	D008765	1.50	<0.005	0.001
			36.50	38.00	D008766	1.50	<0.005	0.001
			38.00	39.50	D008768	1.50	<0.005	0.001
			39.50	41.00	D008769	1.50	<0.005	0.001
			41.00	42.50	D008770	1.50	<0.005	0.001
			42.50	44.00	D008771	1.50	<0.005	0.001
			44.00	45.50	D008772	1.50	0.006	0.006
			45.50	47.00	D008773	1.50	<0.005	0.001
			47.00	48.50	D008774	1.50	<0.005	0.001
			48.50	50.00	D008775	1.50	<0.005	0.001
			50.00	51.50	D008776	1.50	<0.005	0.001
			51.50	53.00	D008778	1.50	0.011	0.011
			53.00	54.50	D008779	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	54.50	56.00	D008780	1.50	<0.005		0.001
	56.00	57.50	D008781	1.50	<0.005		0.001
	57.50	59.00	D008783	1.50	0.016		0.016
	59.00	60.50	D008784	1.50	0.007		0.007
	60.50	62.00	D008785	1.50	0.020		0.020
	62.00	63.50	D008786	1.50	0.006		0.006
	63.50	65.00	D008788	1.50	0.033		0.033
	65.00	66.50	D008789	1.50	0.007		0.007
	66.50	68.00	D008790	1.50	<0.005		0.001
	68.00	69.50	D008791	1.50	0.007		0.007
	69.50	71.00	D008792	1.50	0.005		0.005
	71.00	72.50	D008793	1.50	<0.005		0.001
	72.50	74.00	D008794	1.50	<0.005		0.001
	74.00	75.50	D008795	1.50	<0.005		0.001
	75.50	77.00	D008796	1.50	<0.005		0.001
	77.00	78.50	D008798	1.50	0.005		0.005
	78.50	80.00	D008799	1.50	<0.005		0.001
	80.00	81.50	D008800	1.50	0.006		0.006
	81.50	83.00	D008801	1.50	0.005		0.005
	83.00	84.50	D008803	1.50	<0.005		0.001
	84.50	86.00	D008804	1.50	<0.005		0.001
	86.00	87.50	D008805	1.50	0.045		0.045
	87.50	89.00	D008806	1.50	0.139		0.139
	89.00	90.50	D008808	1.50	0.013		0.013
	90.50	92.00	D008809	1.50	<0.005		0.001
	92.00	93.50	D008810	1.50	0.010		0.010
	93.50	95.00	D008811	1.50	0.030		0.030
	95.00	96.50	D008812	1.50	0.024		0.024
	96.50	98.00	D008813	1.50	0.081		0.081
	98.00	99.50	D008814	1.50	0.064		0.064
	99.50	101.00	D008815	1.50	0.047		0.047
	101.00	102.50	D008816	1.50	0.011		0.011
	102.50	104.00	D008818	1.50	0.019		0.019

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	104.00	105.50	D008819	1.50	0.010		0.010
	105.50	107.00	D008820	1.50	0.018		0.018
	107.00	108.50	D008821	1.50	0.297		0.297
	108.50	110.00	D008822	1.50	0.222		0.222
	110.00	111.50	D008823	1.50	0.046		0.046
	111.50	113.00	D008824	1.50	0.045		0.045
	113.00	114.50	D008825	1.50	<0.005		0.001
	114.50	116.00	D008826	1.50	0.044		0.044
	116.00	117.50	D008828	1.50	0.013		0.013
	117.50	119.00	D008829	1.50	<0.005		0.001
	119.00	120.50	D008830	1.50	<0.005		0.001
	120.50	122.00	D008831	1.50	0.055		0.055
	122.00	123.50	D008832	1.50	<0.005		0.001
	123.50	125.00	D008833	1.50	<0.005		0.001
	125.00	126.50	D008834	1.50	<0.005		0.001
	126.50	128.00	D008835	1.50	0.006		0.006
	128.00	129.50	D008836	1.50	<0.005		0.001
	129.50	131.00	D008838	1.50	0.068		0.068
	131.00	132.50	D008839	1.50	<0.005		0.001
	132.50	134.00	D008840	1.50	<0.005		0.001
	134.00	135.50	D008841	1.50	<0.005		0.001
	135.50	137.00	D008843	1.50	<0.005		0.001
	137.00	138.50	D008844	1.50	<0.005		0.001
	138.50	140.00	D008845	1.50	<0.005		0.001
	140.00	141.50	D008846	1.50	<0.005		0.001
	141.50	143.00	D008848	1.50	0.210		0.210
	143.00	144.50	D008849	1.50	0.325		0.325
	144.50	146.00	D008850	1.50	<0.005		0.001
	146.00	147.50	D008851	1.50	0.012		0.012
	147.50	149.00	D008852	1.50	<0.005		0.001
	149.00	150.50	D008853	1.50	<0.005		0.001
	150.50	152.00	D008854	1.50	<0.005		0.001
	152.00	153.50	D008855	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	153.50	155.00	D008856	1.50	<0.005		0.001
	155.00	156.00	D008858	1.00	<0.005		0.001
	156.00	157.50	D008859	1.50	<0.005		0.001
	157.50	159.00	D008860	1.50	0.010		0.010
	159.00	160.50	D008861	1.50	0.029		0.029
	160.50	162.00	D008862	1.50	<0.005		0.001
	162.00	163.50	D008863	1.50	<0.005		0.001
	163.50	165.00	D008864	1.50	0.008		0.008
	165.00	166.50	D008865	1.50	0.006		0.006
	166.50	168.00	D008866	1.50	0.011		0.011
	168.00	169.50	D008868	1.50	0.009		0.009
	169.50	171.00	D008869	1.50	0.007		0.007
	171.00	172.50	D008870	1.50	0.008		0.008
	172.50	174.00	D008871	1.50	0.006		0.006
	174.00	175.50	D008872	1.50	0.021		0.021
	175.50	177.00	D008873	1.50	0.009		0.009
	177.00	178.50	D008874	1.50	0.008		0.008
	178.50	180.00	D008875	1.50	0.007		0.007
	180.00	181.50	D008876	1.50	0.007		0.007
	181.50	183.00	D008878	1.50	0.216		0.216
	183.00	184.50	D008879	1.50	0.008		0.008
	184.50	186.00	D008880	1.50	0.007		0.007
	186.00	187.50	D008881	1.50	0.009		0.009
	187.50	189.00	D008883	1.50	0.012		0.012
	189.00	190.50	D008884	1.50	0.058		0.058
	190.50	192.00	D008885	1.50	0.014		0.014
	192.00	193.50	D008886	1.50	0.007		0.007
	193.50	195.00	D008888	1.50	0.017		0.017
	195.00	196.50	D008889	1.50	0.009		0.009
	196.50	198.00	D008890	1.50	0.007		0.007
	198.00	199.50	D008891	1.50	0.030		0.030
	199.50	201.00	D008892	1.50	0.019		0.019
	201.00	202.50	D008893	1.50	0.205		0.205

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	202.50	204.00	D008894	1.50	0.085		0.085
	204.00	205.00	D008895	1.00	0.406		0.406
	205.00	206.50	D008896	1.50	0.045		0.045
	206.50	208.00	D008898	1.50	<0.005		0.001
	208.00	209.50	D008899	1.50	0.007		0.007
	209.50	211.00	D008900	1.50	<0.005		0.001
	211.00	212.50	D008901	1.50	<0.005		0.001
	212.50	214.00	D008902	1.50	<0.005		0.001
	214.00	215.50	D008903	1.50	<0.005		0.001
	215.50	217.00	D008904	1.50	<0.005		0.001
	217.00	218.50	D008905	1.50	<0.005		0.001
	218.50	220.00	D008906	1.50	0.005		0.005
	220.00	221.50	D008908	1.50	0.035		0.035
	221.50	223.00	D008909	1.50	0.021		0.021
	223.00	224.50	D008910	1.50	0.083		0.083
	224.50	226.00	D008911	1.50	0.057		0.057
	226.00	227.50	D008912	1.50	0.007		0.007
	227.50	229.00	D008913	1.50	0.008		0.008
	229.00	230.50	D008914	1.50	0.024		0.024
	230.50	232.00	D008915	1.50	<0.005		0.001
	232.00	233.50	D008916	1.50	0.006		0.006
	233.50	235.00	D008918	1.50	0.513		0.513
	235.00	236.50	D008919	1.50	<0.005		0.001
	236.50	238.00	D008920	1.50	<0.005		0.001
	238.00	239.50	D008921	1.50	<0.005		0.001
	239.50	241.00	D008923	1.50	<0.005		0.001
	241.00	242.50	D008924	1.50	<0.005		0.001
	242.50	244.00	D008925	1.50	<0.005		0.001
	244.00	245.50	D008926	1.50	0.019		0.019
	245.50	247.00	D008928	1.50	<0.005		0.001
	247.00	248.50	D008929	1.50	0.054		0.054
	248.50	250.00	D008930	1.50	0.127		0.127
	250.00	251.50	D008931	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			251.50	253.00	D008932	1.50	<0.005		0.001
			253.00	254.50	D008933	1.50	<0.005		0.001
			254.50	256.00	D008934	1.50	0.005		0.005
			256.00	257.50	D008935	1.50	<0.005		0.001
			257.50	259.00	D008936	1.50	<0.005		0.001
			259.00	260.50	D008938	1.50	<0.005		0.001
			260.50	262.00	D008939	1.50	0.007		0.007
			262.00	263.50	D008940	1.50	<0.005		0.001
			263.50	265.00	D008941	1.50	<0.005		0.001
			265.00	266.50	D008942	1.50	<0.005		0.001
			266.50	268.00	D008943	1.50	0.008		0.008
			268.00	269.50	D008944	1.50	0.020		0.020
			269.50	271.00	D008945	1.50	1.105		1.105
			271.00	272.50	D008946	1.50	0.071		0.071
			272.50	274.00	D008948	1.50	0.231		0.231
			274.00	275.50	D008949	1.50	1.715		1.715
			275.50	277.00	D008950	1.50	4.840		4.840
			277.00	278.50	D008951	1.50	4.990		4.990
			278.50	280.00	D008952	1.50	2.730		2.730
			280.00	281.50	D008953	1.50	2.980		2.980
			281.50	283.00	D008954	1.50	2.170		2.170
			283.00	284.50	D008955	1.50	0.917		0.917
			284.50	286.00	D008956	1.50	0.907		0.907
			286.00	287.50	D008958	1.50	0.684		0.684
			287.50	289.00	D008959	1.50	0.395		0.395
			289.00	290.50	D008960	1.50	0.383		0.383
			290.50	292.00	D008961	1.50	1.315		1.315
291.40	291.50	FAI	292.00	293.50	D008963	1.50	0.535		0.535
		<b>Faille 45°</b>	293.50	295.00	D008964	1.50	1.820		1.820
		Zone de faille avec boue de faille.	295.00	296.50	D008965	1.50	1.110		1.110
			296.50	298.00	D008966	1.50	2.220		2.220
			298.00	299.50	D008968	1.50	1.790		1.790
			299.50	301.10	D008969	1.60	0.860		0.860

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
301.10	317.00	TU; FIN; RUB <b>Tuf à cendre/lapillis 55°; Grains fins; Rubané</b> Tuf à cendre/lapillis/ blocs, passage de grains fins aux blocs et passage cisaillé et rubané.	301.10	302.50	D008970	1.40	0.871		0.871
			302.50	304.00	D008971	1.50	0.007		0.007
			304.00	305.00	D008972	1.00	<0.005		0.001
			305.00	306.00	D008973	1.00	0.695		0.695
			306.00	307.50	D008974	1.50	3.270		3.270
			307.50	309.00	D008975	1.50	0.008		0.008
			309.00	310.50	D008976	1.50	0.005		0.005
			310.50	312.00	D008978	1.50	<0.005		0.001
			312.00	313.50	D008979	1.50	<0.005		0.001
			313.50	315.00	D008980	1.50	<0.005		0.001
			315.00	316.00	D008981	1.00	<0.005		0.001
			316.00	317.00	D008982	1.00	<0.005		0.001
			317.00	Fin du sondage Nombre d'échantillons : 209 Nombre d'échantillons QAQC : 30 Longueur totale échantillonnée : 310.50					

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.50	11.00	D008747	M	1.50	2.920	2.920
23.00	24.50	D008757	D008756	1.50	0.006	0.006
36.50	38.00	D008767	G2	1.50	1.690	1.690
50.00	51.50	D008777	D008776	1.50	<0.005	0.001
56.00	57.00	D008782	M1	1.00	<0.005	0.001
62.00	63.50	D008787	H	1.50	0.996	0.996
75.50	77.00	D008797	D008796	1.50	<0.005	0.001
81.50	83.00	D008802	M1	1.50	<0.005	0.001
87.50	89.00	D008807	A3	1.50	0.607	0.607
101.00	102.50	D008817	D008816	1.50	0.005	0.005
114.50	116.00	D008827	H	1.50	1.030	1.030
128.00	129.50	D008837	D008836	1.50	<0.005	0.001
134.00	135.50	D008842	M1	1.50	<0.005	0.001
140.00	141.50	D008847	D2	1.50	0.875	0.875
153.50	155.00	D008857	D008856	1.50	<0.005	0.001
166.50	168.00	D008867	B4	1.50	2.610	2.610
180.00	181.50	D008877	D008876	1.50	0.008	0.008
186.00	187.50	D008882	M1	1.50	<0.005	0.001
192.00	193.50	D008887	M	1.50	3.070	3.070
205.00	206.50	D008897	D008896	1.50	0.020	0.020
218.50	220.00	D008907	H	1.50	0.950	0.950
232.00	233.50	D008917	D008916	1.50	0.009	0.009
238.00	239.50	D008922	M1	1.50	<0.005	0.001
244.00	245.50	D008927	D2	1.50	0.691	0.691
257.50	259.00	D008937	D008936	1.50	<0.005	0.001
271.00	272.50	D008947	A3	1.50	0.599	0.599
284.50	286.00	D008957	D008956	1.50	0.755	0.755
290.50	292.00	D008962	M1	1.50	0.007	0.007
296.50	298.00	D008967	G2	1.50	4.020	4.020
309.00	310.50	D008977	D008976	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-168</b>	Titre minier :	Section :	630800
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-04-17	Date de description :	2010-05-19
	Au : 2010-04-22		

Collet

Azimut : 358.00°  
 Plongée : -60.00°  
 Longueur : 463.90 m

UTM

Est	630 807.4
Nord	5 374 352.8
Élévation	312.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	0.80°	-59.50°	Non
Reflex	8.00	0.30°	-58.70°	Non
Reflex	11.00	0.80°	-59.00°	Non
Reflex	14.00	0.30°	-59.00°	Non
Reflex	17.00	0.60°	-59.40°	Non
Reflex	20.00	0.80°	-59.20°	Non
Reflex	23.00	1.10°	-59.30°	Non
Reflex	26.00	1.50°	-59.40°	Non
Reflex	29.00	1.60°	-59.30°	Non
Reflex	32.00	1.60°	-59.30°	Non
Reflex	35.00	1.80°	-59.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.00°	-59.30°	Non
Reflex	41.00	2.00°	-59.20°	Non
Reflex	44.00	2.20°	-59.30°	Non
Reflex	47.00	2.30°	-59.30°	Non
Reflex	50.00	2.40°	-59.30°	Non
Reflex	53.00	2.50°	-59.30°	Non
Reflex	56.00	2.40°	-59.30°	Non
Reflex	59.00	2.60°	-59.30°	Non
Reflex	62.00	2.50°	-59.30°	Non
Reflex	65.00	2.60°	-59.40°	Non
Reflex	68.00	2.90°	-59.50°	Non
Reflex	71.00	3.40°	-59.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	1.00	MT <b>Mort-terrain</b>							
1.00	463.90	SY; MAS; FIN; MTY <b>Syénite; Roche massive; Grains fins; Grains moyens</b> grenue, sub brêchifications localisations, passage altéré en silice, localement cisailé, altération en calcite et séricite, hématisation et oxydes de carbonâtes, localement magnétique, PY fine diss	1.00	2.50	D003889	1.50	0.008		0.008
			2.50	4.00	D003890	1.50	0.006		0.006
			4.00	5.50	D003891	1.50	0.046		0.046
			5.50	7.00	D003892	1.50	0.043		0.043
			7.00	8.50	D003893	1.50	0.146		0.146
			8.50	10.00	D003894	1.50	0.245		0.245
			10.00	11.50	D003895	1.50	0.181		0.181
			11.50	13.00	D003896	1.50	0.264		0.264
			13.00	14.50	D003897	1.50	0.735		0.735
			14.50	16.00	D003899	1.50	0.741		0.741
			16.00	17.50	D003900	1.50	0.904		0.904
1.00	17.50	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP 0.2-3 cm 80° ac localement trachytique 40-60° ac, légère siliciufication en fin d'éch							
17.50	20.50	SI04; SR02 <b>Silicifié 4; Séricitique 2</b> sub brêchique et très faiblement calcique	17.50	19.00	D003901	1.50	4.990		4.990
			19.00	20.50	D003902	1.50	2.480		2.480
			20.50	21.50	D003903	1.00	0.104		0.104
			21.50	23.00	D003904	1.50	0.519		0.519
			23.00	24.50	D003905	1.50	0.216		0.216
			24.50	26.00	D003906	1.50	0.791		0.791
26.00	35.50	SI03; SR01; HM02 <b>Silicifié 3; Séricitique 1; Hématisé 2</b> brêchique à sub brêchique, fragments anguleux à sub arrondi cm, PY en amas et fine 0.8-2%	26.00	27.50	D003907	1.50	1.465		1.465
			27.50	29.00	D003909	1.50	2.380		2.380
			29.00	30.50	D003910	1.50	9.280		9.280
			30.50	32.00	D003911	1.50	7.150		7.150
			32.00	33.50	D003912	1.50	5.700		5.700
			33.50	34.50	D003913	1.00	>10.0	12.90	12.900
			34.50	35.50	D003914	1.00	>10.0	22.80	22.800
			35.50	37.00	D003915	1.50	2.090		2.090
			37.00	38.50	D003916	1.50	0.167		0.167
			38.50	40.00	D003917	1.50	0.418		0.418
			40.00	41.50	D003919	1.50	0.014		0.014

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			41.50	43.00	D003920	1.50		0.028		0.028
			43.00	44.50	D003921	1.50		0.147		0.147
			44.50	46.00	D003922	1.50		<0.005		0.001
			46.00	47.50	D003923	1.50		0.006		0.006
			47.50	49.00	D003924	1.50		0.010		0.010
			49.00	50.50	D003926	1.50		0.008		0.008
			50.50	52.00	D003927	1.50		<0.005		0.001
			52.00	53.50	D003929	1.50		<0.005		0.001
			53.50	55.00	D003930	1.50		0.078		0.078
			55.00	56.50	D003931	1.50		0.065		0.065
			56.50	58.00	D003932	1.50		<0.005		0.001
			58.00	59.50	D003933	1.50		<0.005		0.001
			59.50	61.00	D003934	1.50		<0.005		0.001
			61.00	62.50	D003935	1.50		<0.005		0.001
			62.50	64.00	D003936	1.50		<0.005		0.001
			64.00	65.50	D003937	1.50		<0.005		0.001
			65.50	67.00	D003939	1.50		0.007		0.007
			67.00	68.50	D003940	1.50		0.018		0.018
			68.50	70.00	D003941	1.50		<0.005		0.001
			70.00	71.50	D003942	1.50		0.084		0.084
71.50	82.00	SY; POR	71.50	73.00	D003943	1.50		0.016		0.016
		<b>Syénite; Porphyrique</b>	73.00	74.50	D003944	1.50		0.154		0.154
		phénocristaux automorphe 0.3-3 cm, oxydes de carbonâtes,	74.50	76.00	D003945	1.50		0.018		0.018
		calcite, SR+, CL+	76.00	77.50	D003946	1.50		<0.005		0.001
			77.50	79.00	D003947	1.50		<0.005		0.001
			79.00	80.50	D003949	1.50		0.011		0.011
			80.50	82.00	D003950	1.50		0.096		0.096
			82.00	83.50	D003951	1.50		0.348		0.348
			83.50	85.00	D003952	1.50		0.059		0.059
			85.00	86.70	D003953	1.70		0.512		0.512
86.70	88.00	SI03; CB06; BL	86.70	88.00	D003954	1.30		1.610		1.610
		<b>Silicifié 3; Carbonaté 6; Potassique blanchi</b>	88.00	89.30	D003955	1.30		0.122		0.122
			89.30	90.50	D003956	1.20		0.402		0.402

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
93.50	107.00	SY; POR; FIN <b>Syénite; Porphyrique; Grains fins</b> phénocristaux automorphe 0.4-2 cm, altération en calcite, séricite, HM+++; PY fine diss	90.50	92.00	D003957	1.50	0.375		0.375
			92.00	93.50	D003959	1.50	0.112		0.112
			93.50	95.00	D003960	1.50	<0.005		0.001
			95.00	96.50	D003961	1.50	<0.005		0.001
			96.50	98.00	D003962	1.50	0.006		0.006
			98.00	99.50	D003963	1.50	<0.005		0.001
			99.50	101.00	D003964	1.50	0.078		0.078
			101.00	102.50	D003966	1.50	<0.005		0.001
			102.50	104.00	D003967	1.50	<0.005		0.001
			104.00	105.50	D003969	1.50	0.352		0.352
			105.50	107.00	D003970	1.50	0.126		0.126
			107.00	108.50	D003971	1.50	0.966		0.966
			108.50	110.00	D003972	1.50	1.070		1.070
			110.00	111.00	D003973	1.00	0.517		0.517
			111.00	112.00	D003974	1.00	0.219		0.219
			112.00	113.00	D003975	1.00	0.017		0.017
			113.00	114.50	D003976	1.50	0.013		0.013
			114.50	116.00	D003977	1.50	0.442		0.442
			116.00	117.00	D003979	1.00	<0.005		0.001
			117.00	118.10	D003980	1.10	<0.005		0.001
118.10	119.50	D003981	1.40	0.018		0.018			
119.50	121.00	D003982	1.50	0.007		0.007			
121.00	122.50	D003983	1.50	<0.005		0.001			
122.50	124.00	D003984	1.50	0.040		0.040			
124.00	125.50	D003985	1.50	0.016		0.016			
125.50	126.50	D003986	1.00	0.013		0.013			
126.50	128.00	D003987	1.50	0.019		0.019			
128.00	129.50	D003989	1.50	0.027		0.027			
129.50	131.00	D003990	1.50	0.014		0.014			
131.00	132.50	D003991	1.50	0.008		0.008			
132.50	134.00	D003992	1.50	0.006		0.006			
134.00	135.50	D003993	1.50	<0.005		0.001			
135.50	137.00	D003994	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
144.50	151.50	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FPm automorphe 0.3-0.5 cm, altération en calcite,	137.00	138.50	D003995	1.50	0.006		0.006
			138.50	140.00	D003996	1.50	<0.005		0.001
			140.00	141.50	D003997	1.50	0.018		0.018
			141.50	143.00	D003999	1.50	0.033		0.033
			143.00	144.50	D004000	1.50	0.007		0.007
			144.50	146.00	D004001	1.50	0.045		0.045
			146.00	147.50	D004002	1.50	0.007		0.007
			147.50	149.00	D004003	1.50	1.070		1.070
			149.00	150.50	D004004	1.50	0.096		0.096
			150.50	151.50	D004006	1.00	0.006		0.006
			151.50	153.00	D004007	1.50	<0.005		0.001
			153.00	154.50	D004009	1.50	0.125		0.125
			154.50	156.00	D004010	1.50	0.010		0.010
			156.00	157.50	D004011	1.50	0.024		0.024
157.50	165.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe ou sub arrondi 0.2-2 cm, altération en calcite	157.50	159.00	D004012	1.50	0.008		0.008
			159.00	160.50	D004013	1.50	0.008		0.008
			160.50	162.00	D004014	1.50	<0.005		0.001
			162.00	163.50	D004015	1.50	<0.005		0.001
			163.50	165.00	D004016	1.50	0.005		0.005
			165.00	166.50	D004017	1.50	0.006		0.006
			166.50	168.00	D004019	1.50	<0.005		0.001
			168.00	169.50	D004020	1.50	<0.005		0.001
			169.50	171.00	D004021	1.50	<0.005		0.001
			171.00	172.50	D004022	1.50	<0.005		0.001
			172.50	174.00	D004023	1.50	<0.005		0.001
			174.00	175.50	D004024	1.50	0.109		0.109
			175.50	176.50	D004025	1.00	0.027		0.027
			176.50	178.00	D004026	1.50	0.014		0.014
178.00	179.50	D004027	1.50	0.006		0.006			
179.50	181.00	D004029	1.50	<0.005		0.001			
180.20	193.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe banchâtre 0.2-2 cm, fortement altéré en calcite	181.00	182.50	D004030	1.50	<0.005		0.001
			182.50	184.00	D004031	1.50	<0.005		0.001
			184.00	185.50	D004032	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			185.50	187.00	D004033	1.50	<0.005		0.001
			187.00	188.50	D004034	1.50	<0.005		0.001
			188.50	190.00	D004035	1.50	<0.005		0.001
			190.00	191.50	D004036	1.50	<0.005		0.001
			191.50	193.00	D004037	1.50	<0.005		0.001
			193.00	194.50	D004039	1.50	0.064		0.064
			194.50	196.00	D004040	1.50	0.016		0.016
			196.00	197.50	D004041	1.50	0.018		0.018
197.50	204.70	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe ou sub arrondi, xénoolithes BO+, HM+++; fortement altéré en calcite	197.50	199.00	D004042	1.50	<0.005		0.001
			199.00	200.50	D004043	1.50	0.006		0.006
			200.50	202.00	D004044	1.50	<0.005		0.001
			202.00	203.50	D004046	1.50	0.045		0.045
			203.50	205.00	D004047	1.50	0.012		0.012
			205.00	206.30	D004049	1.30	0.708		0.708
206.30	208.30	CIS <b>Cisaillement 30°</b> légèrement cisailé	206.30	207.50	D004050	1.20	0.490		0.490
			207.50	209.00	D004051	1.50	0.393		0.393
			209.00	210.50	D004052	1.50	0.009		0.009
			210.50	212.00	D004053	1.50	0.044		0.044
			212.00	213.50	D004054	1.50	0.005		0.005
213.50	221.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP 0.2-1 cm localement chloritisé, altération en calcite	213.50	215.00	D004055	1.50	<0.005		0.001
			215.00	216.50	D004056	1.50	0.031		0.031
			216.50	218.00	D004057	1.50	<0.005		0.001
			218.00	219.50	D004059	1.50	0.005		0.005
			219.50	221.00	D004060	1.50	0.009		0.009
			221.00	222.50	D004061	1.50	0.013		0.013
			222.50	224.00	D004062	1.50	<0.005		0.001
224.00	228.50	SY; POR <b>Syénite; Porphyrique</b> phénocristaux 0.2-1 cm automorphe ou sub arrondi	224.00	225.50	D004063	1.50	<0.005		0.001
			225.50	227.00	D004064	1.50	<0.005		0.001
			227.00	228.50	D004065	1.50	<0.005		0.001
			228.50	230.00	D004066	1.50	<0.005		0.001
			230.00	231.50	D004067	1.50	<0.005		0.001
			231.50	233.00	D004069	1.50	0.005		0.005
			233.00	234.30	D004070	1.30	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
238.00	255.40	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi 0.3-2 cm, altération en calcite	234.30	235.30	D004071	1.00	0.006		0.006
			235.30	236.50	D004072	1.20	<0.005		0.001
			236.50	238.00	D004073	1.50	0.006		0.006
			238.00	239.50	D004074	1.50	0.006		0.006
			239.50	241.00	D004075	1.50	0.005		0.005
			241.00	242.50	D004076	1.50	<0.005		0.001
			242.50	244.00	D004077	1.50	0.005		0.005
			244.00	245.50	D004079	1.50	<0.005		0.001
			245.50	247.00	D004080	1.50	0.055		0.055
			247.00	248.50	D004081	1.50	0.038		0.038
			248.50	250.00	D004082	1.50	0.034		0.034
			250.00	251.50	D004083	1.50	0.007		0.007
			251.50	253.00	D004084	1.50	0.006		0.006
			253.00	254.50	D004086	1.50	0.020		0.020
			254.50	256.00	D004087	1.50	0.006		0.006
259.00	272.50	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe de FP 0.2-2 cm	256.00	257.50	D004089	1.50	0.179		0.179
			257.50	259.00	D004090	1.50	0.054		0.054
			259.00	260.50	D004091	1.50	0.005		0.005
			260.50	262.00	D004092	1.50	0.005		0.005
			262.00	263.50	D004093	1.50	<0.005		0.001
			263.50	265.00	D004094	1.50	<0.005		0.001
			265.00	266.50	D004095	1.50	<0.005		0.001
			266.50	268.00	D004096	1.50	0.009		0.009
			268.00	269.50	D004097	1.50	<0.005		0.001
			269.50	271.00	D004099	1.50	0.008		0.008
			271.00	272.50	D004100	1.50	<0.005		0.001
			272.50	274.00	D004101	1.50	0.272		0.272
			274.00	275.50	D004102	1.50	0.102		0.102
			275.50	276.50	D004103	1.00	0.260		0.260
			276.50	277.50	D004104	1.00	<0.005		0.001
277.50	279.00	D004105	1.50	0.209		0.209			
279.00	280.50	D004106	1.50	0.050		0.050			
280.50	282.00	D004107	1.50	0.016		0.016			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	282.00	283.50	D004109	1.50	0.009		0.009
	283.50	285.00	D004110	1.50	0.017		0.017
	285.00	286.50	D004111	1.50	0.142		0.142
	286.50	288.00	D004112	1.50	0.543		0.543
	288.00	289.50	D004113	1.50	0.022		0.022
	289.50	291.00	D004114	1.50	0.890		0.890
	291.00	292.50	D004115	1.50	1.320		1.320
	292.50	294.00	D004116	1.50	0.365		0.365
	294.00	295.50	D004117	1.50	0.194		0.194
	295.50	297.00	D004119	1.50	<0.005		0.001
	297.00	298.50	D004120	1.50	0.051		0.051
	298.50	300.00	D004121	1.50	0.093		0.093
	300.00	301.50	D004122	1.50	0.037		0.037
	301.50	303.00	D004123	1.50	0.011		0.011
	303.00	304.50	D004124	1.50	0.034		0.034
	304.50	306.00	D004126	1.50	<0.005		0.001
	306.00	307.50	D004127	1.50	0.005		0.005
	307.50	309.00	D004129	1.50	0.008		0.008
	309.00	310.50	D004130	1.50	<0.005		0.001
	310.50	312.00	D004131	1.50	<0.005		0.001
	312.00	313.50	D004132	1.50	0.005		0.005
	313.50	315.00	D004133	1.50	0.007		0.007
	315.00	316.50	D004134	1.50	0.008		0.008
	316.50	318.00	D004135	1.50	0.010		0.010
	318.00	319.50	D004136	1.50	<0.005		0.001
	319.50	321.00	D004137	1.50	<0.005		0.001
	321.00	322.50	D004139	1.50	0.006		0.006
	322.50	324.00	D004140	1.50	0.006		0.006
	324.00	325.50	D004141	1.50	<0.005		0.001
	325.50	327.00	D004142	1.50	<0.005		0.001
	327.00	328.50	D004143	1.50	0.011		0.011
	328.50	330.00	D004144	1.50	0.028		0.028
	330.00	331.50	D004145	1.50	0.011		0.011

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	331.50	333.00	D004146	1.50	<0.005		0.001
	333.00	334.50	D004147	1.50	0.024		0.024
	334.50	336.00	D004149	1.50	0.047		0.047
	336.00	337.50	D004150	1.50	0.006		0.006
	337.50	339.00	D004151	1.50	<0.005		0.001
	339.00	340.50	D004152	1.50	0.008		0.008
	340.50	342.00	D004153	1.50	0.031		0.031
	342.00	343.50	D004154	1.50	0.162		0.162
	343.50	345.00	D004155	1.50	0.038		0.038
	345.00	346.50	D004156	1.50	0.036		0.036
	346.50	348.00	D004157	1.50	<0.005		0.001
	348.00	349.50	D004159	1.50	0.005		0.005
	349.50	351.00	D004160	1.50	<0.005		0.001
	351.00	352.50	D004161	1.50	0.008		0.008
	352.50	354.00	D004162	1.50	<0.005		0.001
	354.00	355.50	D004163	1.50	<0.005		0.001
	355.50	357.00	D004164	1.50	<0.005		0.001
	357.00	358.50	D004166	1.50	<0.005		0.001
	358.50	360.00	D004167	1.50	<0.005		0.001
	360.00	361.50	D004169	1.50	0.007		0.007
	361.50	363.00	D004170	1.50	<0.005		0.001
	363.00	364.50	D004171	1.50	<0.005		0.001
	364.50	366.00	D004172	1.50	0.012		0.012
	366.00	367.50	D004173	1.50	0.017		0.017
	367.50	369.00	D004174	1.50	0.057		0.057
	369.00	370.50	D004175	1.50	0.007		0.007
	370.50	372.00	D004176	1.50	0.008		0.008
	372.00	373.50	D004177	1.50	<0.005		0.001
	373.50	375.00	D004179	1.50	0.020		0.020
	375.00	376.50	D004180	1.50	<0.005		0.001
	376.50	378.00	D004181	1.50	<0.005		0.001
	378.00	379.50	D004182	1.50	<0.005		0.001
	379.50	381.10	D004183	1.60	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	381.10	382.50	D004184	1.40	0.107		0.107
	382.50	384.00	D004185	1.50	0.027		0.027
	384.00	385.50	D004186	1.50	0.027		0.027
	385.50	387.00	D004187	1.50	0.029		0.029
	387.00	388.60	D004189	1.60	0.124		0.124
	388.60	390.00	D004190	1.40	0.037		0.037
	390.00	391.50	D004191	1.50	0.107		0.107
	391.50	393.00	D004192	1.50	0.051		0.051
	393.00	394.50	D004193	1.50	0.059		0.059
	394.50	396.00	D004194	1.50	0.077		0.077
	396.00	397.50	D004195	1.50	0.146		0.146
	397.50	399.00	D004196	1.50	0.080		0.080
	399.00	400.50	D004197	1.50	<0.005		0.001
	400.50	402.00	D004199	1.50	0.037		0.037
	402.00	403.50	D004200	1.50	0.015		0.015
	403.50	405.00	D004201	1.50	0.014		0.014
	405.00	406.50	D004202	1.50	<0.005		0.001
	406.50	408.00	D004203	1.50	<0.005		0.001
	408.00	409.50	D004204	1.50	<0.005		0.001
	409.50	411.00	D004206	1.50	0.006		0.006
	411.00	412.50	D004207	1.50	0.007		0.007
	412.50	414.00	D004209	1.50	0.006		0.006
	414.00	415.50	D004210	1.50	<0.005		0.001
	415.50	417.00	D004211	1.50	0.009		0.009
	417.00	418.50	D004212	1.50	<0.005		0.001
	418.50	420.00	D004213	1.50	0.162		0.162
	420.00	421.50	D004214	1.50	0.089		0.089
	421.50	423.00	D004215	1.50	0.008		0.008
	423.00	424.50	D004216	1.50	<0.005		0.001
	424.50	426.00	D004217	1.50	0.012		0.012
	426.00	427.50	D004219	1.50	<0.005		0.001
	427.50	429.00	D004220	1.50	<0.005		0.001
	429.00	430.50	D004221	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	430.50	432.00	D004222	1.50	<0.005		0.001
	432.00	433.50	D004223	1.50	0.040		0.040
	433.50	435.00	D004224	1.50	<0.005		0.001
	435.00	436.50	D004225	1.50	<0.005		0.001
	436.50	438.00	D004226	1.50	<0.005		0.001
	438.00	439.50	D004227	1.50	<0.005		0.001
	439.50	441.00	D004229	1.50	<0.005		0.001
	441.00	442.50	D004230	1.50	<0.005		0.001
	442.50	444.00	D004231	1.50	<0.005		0.001
	444.00	445.50	D004232	1.50	<0.005		0.001
	445.50	447.00	D004233	1.50	<0.005		0.001
	447.00	448.50	D004234	1.50	0.010		0.010
	448.50	450.00	D004235	1.50	0.136		0.136
	450.00	451.50	D004236	1.50	0.043		0.043
	451.50	453.00	D004237	1.50	0.302		0.302
	453.00	454.50	D004239	1.50	0.042		0.042
	454.50	456.00	D004240	1.50	0.010		0.010
	456.00	457.50	D004241	1.50	<0.005		0.001
	457.50	459.00	D004242	1.50	<0.005		0.001
	459.00	460.50	D004243	1.50	<0.005		0.001
	460.50	462.00	D004244	1.50	0.009		0.009
	462.00	463.00	D004246	1.00	<0.005		0.001
	463.00	463.90	D004247	0.90	<0.005		0.001
463.90	Fin du sondage Nombre d'échantillons : 315 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 462.90						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.00	14.50	D003898	D003897	1.50	0.706	0.706
26.00	26.00	D003908	A3	0.00	0.599	0.599
38.50	40.00	D003918	D003917	1.50	0.025	0.025
47.50	47.50	D003925	M1	0.00	0.011	0.011
50.50	50.50	D003928	B4	0.00	2.660	2.660
64.00	65.50	D003938	D003937	1.50	<0.005	0.001
77.50	77.50	D003948	C4	0.00	1.360	1.360
90.50	92.00	D003958	D003957	1.50	0.393	0.393
99.50	99.50	D003965	M1	0.00	<0.005	0.001
102.50	102.50	D003968	J	0.00	0.784	0.784
114.50	116.00	D003978	D003977	1.50	0.427	0.427
126.50	126.50	D003988	K	0.00	0.991	0.991
140.00	141.50	D003998	D003997	1.50	0.022	0.022
149.00	149.00	D004005	M1	0.00	<0.005	0.001
151.50	151.50	D004008	L	0.00	2.000	2.000
165.00	166.50	D004018	D004017	1.50	<0.005	0.001
178.00	178.00	D004028	M	0.00	3.030	3.030
191.50	193.00	D004038	D004037	1.50	<0.005	0.001
200.50	200.50	D004045	M1	0.00	<0.005	0.001
203.50	203.50	D004048	J	0.00	0.790	0.790
216.50	218.00	D004058	D004057	1.50	0.005	0.005
230.00	230.00	D004068	K	0.00	0.998	0.998
242.50	244.00	D004078	D004077	1.50	0.006	0.006
251.50	251.50	D004085	M1	0.00	<0.005	0.001
254.50	254.50	D004088	L	0.00	2.150	2.150
268.00	269.50	D004098	D004097	1.50	<0.005	0.001
280.50	280.50	D004108	M	0.00	3.070	3.070
294.00	295.50	D004118	D004117	1.50	0.171	0.171
303.00	303.00	D004125	M1	0.00	<0.005	0.001
306.00	306.00	D004128	J	0.00	0.719	0.719
319.50	321.00	D004138	D004137	1.50	<0.005	0.001
333.00	333.00	D004148	K	0.00	1.035	1.035
346.50	348.00	D004158	D004157	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
355.50	355.50	D004165	M1	0.00	<0.005	0.001
358.50	358.50	D004168	L	0.00	1.965	1.965
372.00	373.50	D004178	D004177	1.50	<0.005	0.001
385.50	385.50	D004188	M	0.00	3.190	3.190
399.00	400.50	D004198	D004197	1.50	0.005	0.005
408.00	408.00	D004205	M1	0.00	<0.005	0.001
411.00	411.00	D004208	J	0.00	0.719	0.719
424.50	426.00	D004218	D004217	1.50	0.017	0.017
438.00	438.00	D004228	K	0.00	1.050	1.050
451.50	453.00	D004238	D004237	1.50	0.208	0.208
460.50	460.50	D004245	M1	0.00	<0.005	0.001
463.00	463.00	D004248	L	0.00	2.230	2.230

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-169**

Titre minier :

Section :                      630800

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-22

Date de description :

Au :                      2010-04-26

Collet

UTM

Azimut :                183.00°

Plongée :              -60.00°

Longueur :            407.00 m

Est                      630 808.0

Nord                    5 374 351.3

Élévation             312.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	184.80°	-59.80°	Non
Reflex	8.00	184.80°	-59.80°	Non
Reflex	11.00	185.40°	-59.80°	Non
Reflex	14.00	185.00°	-59.70°	Non
Reflex	17.00	184.90°	-59.80°	Non
Reflex	20.00	185.00°	-59.80°	Non
Reflex	23.00	185.30°	-59.80°	Non
Reflex	26.00	185.40°	-59.80°	Non
Reflex	29.00	185.20°	-59.80°	Non
Reflex	32.00	185.10°	-59.90°	Non
Reflex	35.00	185.30°	-59.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	185.50°	-60.00°	Non
Reflex	41.00	185.70°	-60.00°	Non
Reflex	44.00	185.70°	-60.00°	Non
Reflex	47.00	185.70°	-60.00°	Non
Reflex	50.00	186.10°	-60.10°	Non
Reflex	53.00	186.00°	-60.10°	Non
Reflex	56.00	185.60°	-60.10°	Non
Reflex	59.00	186.20°	-60.20°	Non
Reflex	62.00	186.10°	-60.10°	Non
Reflex	65.00	186.20°	-60.20°	Non
Reflex	68.00	186.30°	-60.20°	Non
Reflex	71.00	186.40°	-60.20°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.70	MT						
		<b>Mort-terrain</b>						
1.70	85.00	SY; FIN; POR	1.70	3.00	D008983	1.30	0.053	0.053
		<b>Syénite; Grains fins; Porphyrique</b>	3.00	4.50	D008984	1.50	0.025	0.025
		Syénite, à gains fins, porphyrique avec de phénocristaux Xmm.	4.50	6.00	D008985	1.50	0.021	0.021
			6.00	7.50	D008986	1.50	0.005	0.005
			7.50	9.00	D008988	1.50	0.047	0.047
			9.00	10.50	D008989	1.50	0.035	0.035
			10.50	12.00	D008990	1.50	<0.005	0.001
			12.00	13.50	D008991	1.50	0.005	0.005
			13.50	15.00	D008992	1.50	<0.005	0.001
			15.00	16.50	D008993	1.50	0.036	0.036
			16.50	18.00	D008994	1.50	<0.005	0.001
			18.00	19.50	D008995	1.50	<0.005	0.001
			19.50	21.00	D008996	1.50	<0.005	0.001
			21.00	22.50	D008998	1.50	<0.005	0.001
			22.50	24.00	D008999	1.50	<0.005	0.001
			24.00	25.50	D009000	1.50	0.006	0.006
			25.50	27.00	D009001	1.50	<0.005	0.001
			27.00	28.50	D009003	1.50	<0.005	0.001
			28.50	30.00	D009004	1.50	0.008	0.008
			30.00	31.50	D009005	1.50	<0.005	0.001
			31.50	33.00	D009006	1.50	<0.005	0.001
			33.00	34.50	D009008	1.50	<0.005	0.001
			34.50	36.00	D009009	1.50	<0.005	0.001
			36.00	37.50	D009010	1.50	<0.005	0.001
			37.50	39.00	D009011	1.50	<0.005	0.001
			39.00	40.50	D009012	1.50	<0.005	0.001
			40.50	42.00	D009013	1.50	<0.005	0.001
			42.00	43.50	D009014	1.50	<0.005	0.001
			43.50	45.00	D009015	1.50	<0.005	0.001
			45.00	46.50	D009016	1.50	0.225	0.225
			46.50	48.00	D009018	1.50	<0.005	0.001
			48.00	49.50	D009019	1.50	0.005	0.005



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.50	100.00	D009058	1.50	<0.005		0.001
	100.00	101.50	D009059	1.50	0.322		0.322
	101.50	103.00	D009060	1.50	0.152		0.152
	103.00	104.50	D009061	1.50	<0.005		0.001
	104.50	106.00	D009062	1.50	<0.005		0.001
	106.00	107.50	D009063	1.50	<0.005		0.001
	107.50	109.00	D009064	1.50	<0.005		0.001
	109.00	110.50	D009065	1.50	<0.005		0.001
	110.50	112.00	D009066	1.50	<0.005		0.001
	112.00	113.50	D009068	1.50	<0.005		0.001
	113.50	115.00	D009069	1.50	0.029		0.029
	115.00	116.50	D009070	1.50	0.007		0.007
	116.50	118.00	D009071	1.50	0.005		0.005
	118.00	119.50	D009072	1.50	0.123		0.123
	119.50	121.00	D009073	1.50	0.409		0.409
	121.00	122.50	D009074	1.50	0.148		0.148
	122.50	124.00	D009075	1.50	0.479		0.479
	124.00	125.50	D009076	1.50	0.666		0.666
	125.50	127.00	D009078	1.50	0.011		0.011
	127.00	128.50	D009079	1.50	<0.005		0.001
	128.50	130.00	D009080	1.50	<0.005		0.001
	130.00	131.50	D009081	1.50	<0.005		0.001
	131.50	133.00	D009083	1.50	0.005		0.005
	133.00	134.50	D009084	1.50	<0.005		0.001
	134.50	136.00	D009085	1.50	0.005		0.005
	136.00	137.50	D009086	1.50	<0.005		0.001
	137.50	139.00	D009088	1.50	<0.005		0.001
	139.00	140.50	D009089	1.50	<0.005		0.001
	140.50	142.00	D009090	1.50	<0.005		0.001
	142.00	143.50	D009091	1.50	<0.005		0.001
	143.50	145.00	D009092	1.50	<0.005		0.001
	145.00	146.50	D009093	1.50	<0.005		0.001
	146.50	148.00	D009094	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			148.00	149.50	D009095	1.50	<0.005		0.001
			149.50	151.00	D009096	1.50	<0.005		0.001
			151.00	152.50	D009098	1.50	<0.005		0.001
			152.50	154.00	D009099	1.50	<0.005		0.001
			154.00	155.50	D009100	1.50	<0.005		0.001
			155.50	157.00	D009101	1.50	<0.005		0.001
			157.00	158.50	D009102	1.50	<0.005		0.001
			158.50	160.00	D009103	1.50	<0.005		0.001
			160.00	161.50	D009104	1.50	<0.005		0.001
			161.50	163.00	D009105	1.50	<0.005		0.001
			163.00	164.50	D009106	1.50	<0.005		0.001
			164.50	166.00	D009108	1.50	<0.005		0.001
			166.00	167.50	D009109	1.50	<0.005		0.001
			167.50	169.00	D009110	1.50	<0.005		0.001
			169.00	170.50	D009111	1.50	<0.005		0.001
			170.50	172.00	D009112	1.50	<0.005		0.001
			172.00	172.80	D009113	0.80	<0.005		0.001
172.80	407.00	SY; MAS; FIN; POR	172.80	174.50	D009114	1.70	0.005		0.005
		<b>Syénite 35°; Roche massive; Grains fins; Porphyrique</b>	174.50	176.00	D009115	1.50	0.326		0.326
		Syénite massive à grains fins avec passage porphyrique avec les	176.00	177.50	D009116	1.50	1.140		1.140
		phénocristaux Xmm.	177.50	179.00	D009118	1.50	0.021		0.021
			179.00	180.50	D009119	1.50	0.007		0.007
			180.50	182.00	D009120	1.50	0.006		0.006
			182.00	183.50	D009121	1.50	<0.005		0.001
			183.50	185.00	D009123	1.50	<0.005		0.001
			185.00	186.50	D009124	1.50	<0.005		0.001
			186.50	188.00	D009125	1.50	<0.005		0.001
			188.00	189.50	D009126	1.50	<0.005		0.001
			189.50	191.00	D009128	1.50	<0.005		0.001
			191.00	192.50	D009129	1.50	<0.005		0.001
			192.50	194.00	D009130	1.50	<0.005		0.001
			194.00	195.50	D009131	1.50	0.036		0.036
			195.50	197.00	D009132	1.50	0.027		0.027

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.00	198.50	D009133	1.50	0.016		0.016
	198.50	200.00	D009134	1.50	0.078		0.078
	200.00	201.50	D009135	1.50	0.009		0.009
	201.50	203.00	D009136	1.50	0.010		0.010
	203.00	204.30	D009138	1.30	0.009		0.009
	204.30	206.00	D009139	1.70	0.006		0.006
	206.00	207.50	D009140	1.50	0.008		0.008
	207.50	209.00	D009141	1.50	0.414		0.414
	209.00	210.50	D009142	1.50	2.070		2.070
	210.50	212.00	D009143	1.50	2.510		2.510
	212.00	213.50	D009144	1.50	0.114		0.114
	213.50	215.00	D009145	1.50	0.186		0.186
	215.00	216.50	D009146	1.50	<0.005		0.001
	216.50	218.00	D009148	1.50	1.195		1.195
	218.00	219.50	D009149	1.50	0.827		0.827
	219.50	221.00	D009150	1.50	<0.005		0.001
	221.00	222.50	D009151	1.50	0.009		0.009
	222.50	224.00	D009152	1.50	0.008		0.008
	224.00	225.50	D009153	1.50	0.005		0.005
	225.50	227.00	D009154	1.50	0.028		0.028
	227.00	228.50	D009155	1.50	0.444		0.444
	228.50	230.00	D009156	1.50	0.639		0.639
	230.00	231.50	D009158	1.50	3.210		3.210
	231.50	233.00	D009159	1.50	3.380		3.380
	233.00	234.50	D009160	1.50	2.410		2.410
	234.50	236.00	D009161	1.50	2.270		2.270
	236.00	237.50	D009163	1.50	3.340		3.340
	237.50	239.00	D009164	1.50	1.385		1.385
	239.00	240.50	D009165	1.50	2.980		2.980
	240.50	242.00	D009166	1.50	3.780		3.780
	242.00	243.50	D009168	1.50	4.740		4.740
	243.50	245.00	D009169	1.50	3.520		3.520
	245.00	246.50	D009170	1.50	2.100		2.100

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.50	248.00	D009171	1.50	3.670		3.670
	248.00	249.50	D009172	1.50	1.350		1.350
	249.50	251.00	D009173	1.50	0.631		0.631
	251.00	252.50	D009174	1.50	0.144		0.144
	252.50	254.00	D009175	1.50	0.016		0.016
	254.00	255.50	D009176	1.50	0.025		0.025
	255.50	257.00	D009178	1.50	0.053		0.053
	257.00	258.50	D009179	1.50	0.413		0.413
	258.50	260.00	D009180	1.50	0.063		0.063
	260.00	261.50	D009181	1.50	0.022		0.022
	261.50	263.00	D009182	1.50	0.008		0.008
	263.00	264.50	D009183	1.50	0.014		0.014
	264.50	266.00	D009184	1.50	0.698		0.698
	266.00	267.50	D009185	1.50	0.110		0.110
	267.50	269.00	D009186	1.50	0.031		0.031
	269.00	270.50	D009188	1.50	0.213		0.213
	270.50	272.00	D009189	1.50	1.490		1.490
	272.00	273.50	D009190	1.50	0.663		0.663
	273.50	275.00	D009191	1.50	0.797		0.797
	275.00	276.50	D009192	1.50	0.114		0.114
	276.50	278.00	D009193	1.50	0.102		0.102
	278.00	279.50	D009194	1.50	0.035		0.035
	279.50	281.00	D009195	1.50	1.360		1.360
	281.00	282.50	D009196	1.50	1.740		1.740
	282.50	284.00	D009198	1.50	0.860		0.860
	284.00	285.50	D009199	1.50	0.547		0.547
	285.50	287.00	D009200	1.50	0.302		0.302
	287.00	288.50	D009201	1.50	0.098		0.098
	288.50	290.00	D009203	1.50	0.062		0.062
	290.00	291.50	D009204	1.50	0.067		0.067
	291.50	293.00	D009205	1.50	0.126		0.126
	293.00	294.50	D009206	1.50	0.072		0.072
	294.50	296.00	D009208	1.50	0.152		0.152

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.00	297.50	D009209	1.50	0.232		0.232
	297.50	299.00	D009210	1.50	0.250		0.250
	299.00	300.50	D009211	1.50	0.229		0.229
	300.50	302.00	D009212	1.50	0.009		0.009
	302.00	303.50	D009213	1.50	0.082		0.082
	303.50	305.00	D009214	1.50	0.120		0.120
	305.00	306.50	D009215	1.50	<0.005		0.001
	306.50	308.00	D009216	1.50	<0.005		0.001
	308.00	309.50	D009218	1.50	<0.005		0.001
	309.50	311.00	D009219	1.50	<0.005		0.001
	311.00	312.50	D009220	1.50	<0.005		0.001
	312.50	314.00	D009221	1.50	<0.005		0.001
	314.00	315.50	D009222	1.50	<0.005		0.001
	315.50	317.00	D009223	1.50	0.149		0.149
	317.00	318.50	D009224	1.50	0.005		0.005
	318.50	320.00	D009225	1.50	<0.005		0.001
	320.00	321.50	D009226	1.50	<0.005		0.001
	321.50	323.00	D009228	1.50	<0.005		0.001
	323.00	324.50	D009229	1.50	<0.005		0.001
	324.50	326.00	D009230	1.50	<0.005		0.001
	326.00	327.50	D009231	1.50	<0.005		0.001
	327.50	329.00	D009232	1.50	0.250		0.250
	329.00	330.50	D009233	1.50	0.039		0.039
	330.50	332.00	D009234	1.50	0.077		0.077
	332.00	333.50	D009235	1.50	0.026		0.026
	333.50	335.00	D009236	1.50	<0.005		0.001
	335.00	336.50	D009238	1.50	<0.005		0.001
	336.50	338.00	D009239	1.50	<0.005		0.001
	338.00	339.50	D009240	1.50	0.042		0.042
	339.50	341.00	D009241	1.50	0.327		0.327
	341.00	342.50	D009243	1.50	1.445		1.445
	342.50	344.00	D009244	1.50	1.365		1.365
	344.00	345.50	D009245	1.50	0.332		0.332

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D009246	1.50	0.133		0.133
	347.00	348.50	D009248	1.50	0.466		0.466
	348.50	350.00	D009249	1.50	0.588		0.588
	350.00	351.50	D009250	1.50	0.811		0.811
	351.50	353.00	D009251	1.50	0.090		0.090
	353.00	354.50	D009252	1.50	0.262		0.262
	354.50	356.00	D009253	1.50	0.587		0.587
	356.00	357.50	D009254	1.50	0.390		0.390
	357.50	359.00	D009255	1.50	0.172		0.172
	359.00	360.50	D009256	1.50	0.027		0.027
	360.50	362.00	D009258	1.50	0.010		0.010
	362.00	363.50	D009259	1.50	0.018		0.018
	363.50	365.00	D009260	1.50	0.010		0.010
	365.00	366.50	D009261	1.50	0.009		0.009
	366.50	368.00	D009262	1.50	0.229		0.229
	368.00	369.50	D009263	1.50	0.774		0.774
	369.50	371.00	D009264	1.50	0.063		0.063
	371.00	372.50	D009265	1.50	0.027		0.027
	372.50	374.00	D009266	1.50	0.044		0.044
	374.00	375.50	D009268	1.50	0.079		0.079
	375.50	377.00	D009269	1.50	0.024		0.024
	377.00	378.50	D009270	1.50	0.006		0.006
	378.50	380.00	D009271	1.50	0.027		0.027
	380.00	381.50	D009272	1.50	0.008		0.008
	381.50	383.00	D009273	1.50	0.134		0.134
	383.00	384.50	D009274	1.50	0.063		0.063
	384.50	386.00	D009275	1.50	0.118		0.118
	386.00	387.50	D009276	1.50	0.099		0.099
	387.50	389.00	D009278	1.50	1.775		1.775
	389.00	390.50	D009279	1.50	0.629		0.629
	390.50	392.00	D009280	1.50	0.022		0.022
	392.00	393.50	D009281	1.50	0.156		0.156
	393.50	395.00	D009283	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	395.00	396.50	D009284	1.50	0.524		0.524
	396.50	398.00	D009285	1.50	0.090		0.090
	398.00	399.50	D009286	1.50	1.665		1.665
	399.50	401.00	D009288	1.50	2.210		2.210
	401.00	402.50	D009289	1.50	0.239		0.239
	402.50	404.00	D009290	1.50	0.458		0.458
	404.00	405.50	D009291	1.50	0.515		0.515
	405.50	407.00	D009292	1.50	0.255		0.255
407.00	Fin du sondage Nombre d'échantillons : 271 Nombre d'échantillons QAQC : 39 Longueur totale échantillonnée : 405.30						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	7.50	D008987	C4	1.50	0.809	0.809
19.50	21.00	D008997	D008996	1.50	<0.005	0.001
25.50	27.00	D009002	M1	1.50	<0.005	0.001
31.50	33.00	D009007	D2	1.50	0.820	0.820
45.00	46.50	D009017	D009016	1.50	0.104	0.104
58.50	60.00	D009027	M	1.50	2.840	2.840
72.00	73.50	D009037	D009036	1.50	2.960	2.960
78.00	79.50	D009042	M1	1.50	0.005	0.005
84.00	85.00	D009047	G2	1.00	4.130	4.130
97.00	98.50	D009057	D009056	1.50	0.007	0.007
110.50	112.00	D009067	H	1.50	0.970	0.970
124.00	125.50	D009077	D009076	1.50	0.691	0.691
130.00	131.50	D009082	M1	1.50	0.005	0.005
136.00	137.50	D009087	A3	1.50	0.610	0.610
149.50	151.00	D009097	D009096	1.50	0.006	0.006
163.00	164.50	D009107	B4	1.50	2.620	2.620
176.00	177.50	D009117	D009116	1.50	1.195	1.195
182.00	183.50	D009122	M1	1.50	<0.005	0.001
188.00	189.50	D009127	C4	1.50	1.340	1.340
201.50	203.00	D009137	D009136	1.50	0.014	0.014
215.00	216.50	D009147	D2	1.50	0.839	0.839
228.50	230.00	D009157	D009156	1.50	0.609	0.609
234.50	236.00	D009162	M1	1.50	<0.005	0.001
240.50	242.00	D009167	M	1.50	3.090	3.090
254.00	255.50	D009177	D009176	1.50	0.024	0.024
267.50	269.00	D009187	G2	1.50	4.030	4.030
281.00	282.50	D009197	D009196	1.50	1.835	1.835
287.00	288.50	D009202	M1	1.50	<0.005	0.001
293.00	294.50	D009207	H	1.50	0.971	0.971
306.50	308.00	D009217	D009216	1.50	<0.005	0.001
320.00	321.00	D009227	A3	1.00	0.621	0.621
333.50	335.00	D009237	D009236	1.50	<0.005	0.001
339.50	341.00	D009242	M1	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
345.50	347.00	D009247	G2	1.50	4.060	4.060
359.00	360.50	D009257	D009256	1.50	0.020	0.020
372.50	374.00	D009267	C4	1.50	1.290	1.290
386.00	387.50	D009277	D009276	1.50	0.094	0.094
392.00	393.50	D009282	M1	1.50	<0.005	0.001
398.00	399.50	D009287	D2	1.50	0.816	0.816



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-170**

Titre minier :

Section :                      630800

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-26

Date de description :

Au :                      2010-05-01

Collet

UTM

Azimut :                0.00°

Est                      630 799.8

Plongée :              -60.00°

Nord                    5 374 302.3

Longueur :            467.00 m

Élévation              306.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	2.80°	-59.50°	Non
Reflex	8.00	2.40°	-59.30°	Non
Reflex	11.00	2.70°	-59.30°	Non
Reflex	14.00	2.70°	-59.40°	Non
Reflex	17.00	2.00°	-58.70°	Non
Reflex	20.00	2.10°	-58.70°	Non
Reflex	23.00	2.20°	-58.70°	Non
Reflex	26.00	1.70°	-58.60°	Non
Reflex	29.00	2.20°	-58.80°	Non
Reflex	32.00	1.60°	-58.30°	Non
Reflex	35.00	1.60°	-58.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.80°	-58.30°	Non
Reflex	41.00	1.90°	-58.50°	Non
Reflex	44.00	1.70°	-58.30°	Non
Reflex	47.00	1.90°	-58.50°	Non
Reflex	50.00	2.20°	-58.60°	Non
Reflex	53.00	2.30°	-58.80°	Non
Reflex	56.00	1.40°	-58.30°	Non
Reflex	59.00	1.60°	-58.80°	Non
Reflex	62.00	1.30°	-58.60°	Non
Reflex	65.00	2.20°	-58.70°	Non
Reflex	68.00	1.60°	-58.60°	Non
Reflex	71.00	1.60°	-58.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.70	MT						
		<b>Mort-terrain</b>						
2.70	467.00	SY; FIN; POR	2.70	4.00	D009293	1.30	0.471	0.471
		<b>Syénite; Grains fins; Porphyrique</b>	4.00	5.50	D009294	1.50	6.850	6.850
		Syénite à grains fins avec passage porphyrique, phénocristaux Xmm.	5.50	7.00	D009295	1.50	0.139	0.139
			7.00	8.50	D009296	1.50	0.006	0.006
			8.50	10.00	D009298	1.50	0.022	0.022
			10.00	11.50	D009299	1.50	<0.005	0.001
11.00	16.00	FRC	11.50	13.00	D009300	1.50	0.013	0.013
		<b>Fracturé</b>	13.00	14.50	D009301	1.50	0.008	0.008
		Zone fracturée et oxydée.	14.50	16.00	D009302	1.50	1.525	1.525
			16.00	17.50	D009303	1.50	1.505	1.505
			17.50	19.00	D009304	1.50	4.250	4.250
			19.00	20.50	D009305	1.50	5.100	5.100
			20.50	22.00	D009306	1.50	0.807	0.807
			22.00	23.50	D009308	1.50	1.175	1.175
			23.50	25.00	D009309	1.50	0.105	0.105
			25.00	26.50	D009310	1.50	0.260	0.260
			26.50	28.00	D009311	1.50	0.317	0.317
			28.00	29.50	D009312	1.50	0.108	0.108
			29.50	31.00	D009313	1.50	<0.005	0.001
			31.00	32.50	D009314	1.50	<0.005	0.001
			32.50	34.00	D009315	1.50	<0.005	0.001
			34.00	35.50	D009316	1.50	0.007	0.007
			35.50	37.00	D009318	1.50	<0.005	0.001
			37.00	38.50	D009319	1.50	<0.005	0.001
			38.50	40.00	D009320	1.50	<0.005	0.001
			40.00	41.50	D009321	1.50	0.012	0.012
			41.50	43.00	D009323	1.50	0.021	0.021
			43.00	44.50	D009324	1.50	<0.005	0.001
			44.50	46.00	D009325	1.50	<0.005	0.001
			46.00	47.50	D009326	1.50	0.008	0.008
			47.50	49.00	D009328	1.50	0.044	0.044

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.00	50.50	D009329	1.50	<0.005		0.001
	50.50	52.00	D009330	1.50	0.005		0.005
	52.00	53.50	D009331	1.50	0.932		0.932
	53.50	55.00	D009332	1.50	0.033		0.033
	55.00	56.50	D009333	1.50	0.007		0.007
	56.50	58.00	D009334	1.50	0.016		0.016
	58.00	59.50	D009335	1.50	0.006		0.006
	59.50	61.00	D009336	1.50	0.025		0.025
	61.00	62.50	D009338	1.50	0.054		0.054
	62.50	64.00	D009339	1.50	0.102		0.102
	64.00	65.50	D009340	1.50	0.570		0.570
	65.50	67.00	D009341	1.50	0.195		0.195
	67.00	68.50	D009342	1.50	0.030		0.030
	68.50	70.00	D009343	1.50	<0.005		0.001
	70.00	71.50	D009344	1.50	0.069		0.069
	71.50	73.00	D009345	1.50	0.098		0.098
	73.00	74.50	D009346	1.50	0.027		0.027
	74.50	76.00	D009348	1.50	0.069		0.069
	76.00	77.50	D009349	1.50	0.009		0.009
	77.50	79.00	D009350	1.50	0.056		0.056
	79.00	80.50	D009351	1.50	0.047		0.047
	80.50	82.00	D009352	1.50	0.132		0.132
	82.00	83.50	D009353	1.50	1.800		1.800
	83.50	85.00	D009354	1.50	0.315		0.315
	85.00	86.50	D009355	1.50	<0.005		0.001
	86.50	88.00	D009356	1.50	<0.005		0.001
	88.00	89.50	D009358	1.50	0.136		0.136
	89.50	91.00	D009359	1.50	0.232		0.232
	91.00	92.50	D009360	1.50	<0.005		0.001
	92.50	94.00	D009361	1.50	0.885		0.885
	94.00	95.50	D009363	1.50	0.451		0.451
	95.50	97.00	D009364	1.50	<0.005		0.001
	97.00	98.50	D009365	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	98.50	100.00	D009366	1.50	<0.005		0.001	
	100.00	101.50	D009368	1.50	<0.005		0.001	
	101.50	103.00	D009369	1.50	0.013		0.013	
	103.00	104.50	D009370	1.50	0.010		0.010	
	104.50	106.00	D009371	1.50	0.008		0.008	
	106.00	107.50	D009372	1.50	0.009		0.009	
	107.50	109.00	D009373	1.50	1.130		1.130	
	109.00	110.00	D009374	1.00	0.015		0.015	
	110.00	111.50	D009375	1.50	0.485		0.485	
	111.50	113.00	D009376	1.50	0.012		0.012	
	113.00	114.50	D009378	1.50	<0.005		0.001	
	114.50	116.00	D009379	1.50	<0.005		0.001	
	116.00	117.50	D009380	1.50	0.009		0.009	
	117.50	119.00	D009381	1.50	0.008		0.008	
	119.00	120.50	D009382	1.50	0.010		0.010	
	120.50	122.00	D009383	1.50	0.030		0.030	
	122.00	123.50	D009384	1.50	0.009		0.009	
	123.50	125.00	D009385	1.50	0.551		0.551	
	125.00	126.50	D009386	1.50	0.126		0.126	
	126.50	128.00	D009388	1.50	0.048		0.048	
	128.00	129.50	D009389	1.50	0.090		0.090	
	129.50	131.00	D009390	1.50	0.045		0.045	
131.00	143.00	SY; PT	131.00	132.50	D009391	1.50	0.231	0.231
		<b>Syénite 35°; Porphyre trachytique</b>	132.50	134.00	D009392	1.50	0.153	0.153
		Syénite à texture trachytique avec porphyre qui sont orienté ±	134.00	135.50	D009393	1.50	0.220	0.220
		35° ac.	135.50	137.00	D009394	1.50	0.434	0.434
			137.00	138.50	D009395	1.50	0.343	0.343
			138.50	140.00	D009396	1.50	0.181	0.181
			140.00	141.50	D009398	1.50	1.460	1.460
			141.50	143.00	D009399	1.50	0.349	0.349
			143.00	144.50	D009400	1.50	0.164	0.164
			144.50	146.00	D009401	1.50	0.161	0.161
			146.00	147.50	D009403	1.50	0.046	0.046

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.50	149.00	D009404	1.50	0.009		0.009
	149.00	150.50	D009405	1.50	0.018		0.018
	150.50	152.00	D009406	1.50	0.017		0.017
	152.00	153.50	D009408	1.50	0.006		0.006
	153.50	155.00	D009409	1.50	0.005		0.005
	155.00	156.50	D009410	1.50	<0.005		0.001
	156.50	158.00	D009411	1.50	0.005		0.005
	158.00	159.50	D009412	1.50	0.006		0.006
	159.50	161.00	D009413	1.50	<0.005		0.001
	161.00	162.50	D009414	1.50	0.028		0.028
	162.50	164.00	D009415	1.50	0.012		0.012
	164.00	165.50	D009416	1.50	<0.005		0.001
	165.50	167.00	D009418	1.50	<0.005		0.001
	167.00	168.50	D009419	1.50	0.021		0.021
	168.50	170.00	D009420	1.50	0.535		0.535
	170.00	171.50	D009421	1.50	0.011		0.011
	171.50	173.00	D009422	1.50	0.007		0.007
	173.00	174.50	D009423	1.50	0.042		0.042
	174.50	176.00	D009424	1.50	0.494		0.494
	176.00	177.50	D009425	1.50	0.247		0.247
	177.50	179.00	D009426	1.50	0.005		0.005
	179.00	180.50	D009428	1.50	0.006		0.006
	180.50	182.00	D009429	1.50	0.007		0.007
	182.00	183.50	D009430	1.50	0.008		0.008
	183.50	185.00	D009431	1.50	0.073		0.073
	185.00	186.50	D009432	1.50	0.071		0.071
	186.50	188.00	D009433	1.50	0.071		0.071
	188.00	189.50	D009434	1.50	0.058		0.058
	189.50	191.00	D009435	1.50	0.033		0.033
	191.00	192.50	D009436	1.50	0.063		0.063
	192.50	194.00	D009438	1.50	0.005		0.005
	194.00	195.50	D009439	1.50	0.012		0.012
	195.50	197.00	D009440	1.50	0.028		0.028

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.00	198.50	D009441	1.50	0.005		0.005
	198.50	200.00	D009443	1.50	0.007		0.007
	200.00	201.50	D009444	1.50	0.010		0.010
	201.50	203.00	D009445	1.50	0.157		0.157
	203.00	204.50	D009446	1.50	0.343		0.343
	204.50	206.00	D009448	1.50	0.314		0.314
	206.00	207.50	D009449	1.50	<0.005		0.001
	207.50	209.00	D009450	1.50	<0.005		0.001
	209.00	210.50	D009451	1.50	0.219		0.219
	210.50	212.00	D009452	1.50	0.023		0.023
	212.00	213.50	D009453	1.50	<0.005		0.001
	213.50	215.00	D009454	1.50	0.006		0.006
	215.00	216.50	D009455	1.50	<0.005		0.001
	216.50	218.00	D009456	1.50	<0.005		0.001
	218.00	219.50	D009458	1.50	0.083		0.083
	219.50	221.00	D009459	1.50	0.044		0.044
	221.00	222.50	D009460	1.50	<0.005		0.001
	222.50	224.00	D009461	1.50	<0.005		0.001
	224.00	225.50	D009462	1.50	<0.005		0.001
	225.50	227.00	D009463	1.50	0.450		0.450
	227.00	228.50	D009464	1.50	0.011		0.011
	228.50	230.00	D009465	1.50	<0.005		0.001
	230.00	231.50	D009466	1.50	0.007		0.007
	231.50	233.00	D009468	1.50	0.012		0.012
	233.00	234.50	D009469	1.50	<0.005		0.001
	234.50	236.00	D009470	1.50	<0.005		0.001
	236.00	237.50	D009471	1.50	<0.005		0.001
	237.50	239.00	D009472	1.50	<0.005		0.001
	239.00	240.50	D009473	1.50	<0.005		0.001
	240.50	242.00	D009474	1.50	<0.005		0.001
	242.00	243.50	D009475	1.50	<0.005		0.001
	243.50	245.00	D009476	1.50	0.030		0.030
	245.00	246.50	D009478	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.50	248.00	D009479	1.50	0.089		0.089
	248.00	249.50	D009480	1.50	0.091		0.091
	249.50	251.00	D009481	1.50	0.007		0.007
	251.00	252.50	D009483	1.50	0.007		0.007
	252.50	254.00	D009484	1.50	0.011		0.011
	254.00	255.50	D009485	1.50	0.008		0.008
	255.50	257.00	D009486	1.50	0.096		0.096
	257.00	258.50	D009488	1.50	0.800		0.800
	258.50	260.00	D009489	1.50	0.303		0.303
	260.00	261.50	D009490	1.50	0.006		0.006
	261.50	263.00	D009491	1.50	0.484		0.484
	263.00	264.50	D009492	1.50	0.305		0.305
	264.50	266.00	D009493	1.50	<0.005		0.001
	266.00	267.50	D009494	1.50	0.453		0.453
	267.50	269.00	D009495	1.50	0.268		0.268
	269.00	270.50	D009496	1.50	0.132		0.132
	270.50	272.00	D009498	1.50	0.009		0.009
	272.00	273.50	D009499	1.50	0.010		0.010
	273.50	275.00	D009500	1.50	0.016		0.016
	275.00	276.50	D009501	1.50	0.024		0.024
	276.50	278.00	D009503	1.50	0.335		0.335
	278.00	279.50	D009504	1.50	<0.005		0.001
	279.50	281.00	D009505	1.50	<0.005		0.001
	281.00	282.50	D009506	1.50	<0.005		0.001
	282.50	284.00	D009508	1.50	<0.005		0.001
	284.00	285.50	D009509	1.50	<0.005		0.001
	285.50	287.00	D009510	1.50	<0.005		0.001
	287.00	288.50	D009511	1.50	0.026		0.026
	288.50	290.00	D009512	1.50	0.006		0.006
	290.00	291.50	D009513	1.50	0.094		0.094
	291.50	293.00	D009514	1.50	0.051		0.051
	293.00	294.50	D009515	1.50	<0.005		0.001
	294.50	296.00	D009516	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.00	297.50	D009518	1.50	<0.005		0.001
	297.50	299.00	D009519	1.50	0.005		0.005
	299.00	300.50	D009520	1.50	<0.005		0.001
	300.50	302.00	D009521	1.50	0.009		0.009
	302.00	303.50	D009522	1.50	0.010		0.010
	303.50	305.00	D009523	1.50	0.061		0.061
	305.00	306.50	D009524	1.50	0.288		0.288
	306.50	308.00	D009525	1.50	0.007		0.007
	308.00	309.50	D009526	1.50	0.008		0.008
	309.50	311.00	D009528	1.50	0.006		0.006
	311.00	312.50	D009529	1.50	<0.005		0.001
	312.50	314.00	D009530	1.50	<0.005		0.001
	314.00	315.50	D009531	1.50	0.794		0.794
	315.50	317.00	D009532	1.50	0.594		0.594
	317.00	318.50	D009533	1.50	1.980		1.980
	318.50	320.00	D009534	1.50	0.679		0.679
	320.00	321.50	D009535	1.50	0.012		0.012
	321.50	323.00	D009536	1.50	0.005		0.005
	323.00	324.50	D009538	1.50	0.005		0.005
	324.50	326.00	D009539	1.50	0.076		0.076
	326.00	327.50	D009540	1.50	0.005		0.005
	327.50	329.00	D009541	1.50	0.400		0.400
	329.00	330.50	D009543	1.50	0.124		0.124
	330.50	332.00	D009544	1.50	0.423		0.423
	332.00	333.50	D009545	1.50	0.771		0.771
	333.50	335.00	D009546	1.50	0.100		0.100
	335.00	336.50	D009548	1.50	0.170		0.170
	336.50	338.00	D009549	1.50	0.041		0.041
	338.00	339.50	D009550	1.50	0.108		0.108
	339.50	341.00	D009551	1.50	<0.005		0.001
	341.00	342.50	D009552	1.50	0.005		0.005
	342.50	344.00	D009553	1.50	<0.005		0.001
	344.00	345.50	D009554	1.50	0.007		0.007



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D009555	1.50	0.007		0.007
	347.00	348.50	D009556	1.50	<0.005		0.001
	348.50	350.00	D009558	1.50	<0.005		0.001
	350.00	351.50	D009559	1.50	0.006		0.006
	351.50	353.00	D009560	1.50	<0.005		0.001
	353.00	354.50	D009561	1.50	<0.005		0.001
	354.50	356.00	D009562	1.50	0.008		0.008
	356.00	357.50	D009563	1.50	0.021		0.021
	357.50	359.00	D009564	1.50	0.089		0.089
	359.00	360.50	D009565	1.50	0.153		0.153
	360.50	362.00	D009566	1.50	0.668		0.668
	362.00	363.50	D009568	1.50	0.697		0.697
	363.50	365.00	D009569	1.50	<0.005		0.001
	365.00	366.50	D009570	1.50	<0.005		0.001
	366.50	368.00	D009571	1.50	<0.005		0.001
	368.00	369.50	D009572	1.50	<0.005		0.001
	369.50	371.00	D009573	1.50	0.005		0.005
	371.00	372.50	D009574	1.50	0.018		0.018
	372.50	374.00	D009575	1.50	0.008		0.008
	374.00	375.50	D009576	1.50	0.006		0.006
	375.50	377.00	D009578	1.50	0.006		0.006
	377.00	378.50	D009579	1.50	<0.005		0.001
	378.50	380.00	D009580	1.50	0.258		0.258
	380.00	381.50	D009581	1.50	<0.005		0.001
	381.50	383.00	D009583	1.50	0.037		0.037
	383.00	384.50	D009584	1.50	<0.005		0.001
	384.50	386.00	D009585	1.50	0.310		0.310
	386.00	387.50	D009586	1.50	0.112		0.112
	387.50	389.00	D009588	1.50	0.235		0.235
	389.00	390.50	D009589	1.50	0.104		0.104
	390.50	392.00	D009590	1.50	<0.005		0.001
	392.00	393.50	D009591	1.50	<0.005		0.001
	393.50	395.00	D009592	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	395.00	396.50	D009593	1.50	0.381		0.381
	396.50	398.00	D009594	1.50	0.014		0.014
	398.00	399.50	D009595	1.50	<0.005		0.001
	399.50	401.00	D009596	1.50	<0.005		0.001
	401.00	402.50	D009598	1.50	<0.005		0.001
	402.50	404.00	D009599	1.50	0.006		0.006
	404.00	405.50	D009600	1.50	0.005		0.005
	405.50	407.00	D009601	1.50	0.044		0.044
	407.00	408.50	D009602	1.50	0.005		0.005
	408.50	410.00	D009603	1.50	<0.005		0.001
	410.00	411.50	D009604	1.50	<0.005		0.001
	411.50	413.00	D009605	1.50	<0.005		0.001
	413.00	414.50	D009606	1.50	<0.005		0.001
	414.50	416.00	D009608	1.50	0.010		0.010
	416.00	417.50	D009609	1.50	0.015		0.015
	417.50	419.00	D009610	1.50	0.382		0.382
	419.00	420.50	D009611	1.50	0.246		0.246
	420.50	422.00	D009612	1.50	0.043		0.043
	422.00	423.50	D009613	1.50	0.056		0.056
	423.50	425.00	D009614	1.50	0.005		0.005
	425.00	426.50	D009615	1.50	<0.005		0.001
	426.50	428.00	D009616	1.50	<0.005		0.001
	428.00	429.50	D009618	1.50	0.018		0.018
	429.50	431.00	D009619	1.50	0.068		0.068
	431.00	432.50	D009620	1.50	0.052		0.052
	432.50	434.00	D009621	1.50	0.100		0.100
	434.00	435.50	D009623	1.50	0.770		0.770
	435.50	437.00	D009624	1.50	0.433		0.433
	437.00	438.50	D009625	1.50	0.018		0.018
	438.50	440.00	D009626	1.50	0.011		0.011
	440.00	441.50	D009628	1.50	0.102		0.102
	441.50	443.00	D009629	1.50	0.122		0.122
	443.00	444.50	D009630	1.50	0.244		0.244

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	444.50	446.00	D009631	1.50	0.015		0.015
	446.00	447.50	D009632	1.50	0.005		0.005
	447.50	449.00	D009633	1.50	0.010		0.010
	449.00	450.50	D009634	1.50	<0.005		0.001
	450.50	452.00	D009635	1.50	<0.005		0.001
	452.00	453.50	D009636	1.50	<0.005		0.001
	453.50	455.00	D009638	1.50	<0.005		0.001
	455.00	456.50	D009639	1.50	<0.005		0.001
	456.50	458.00	D009640	1.50	0.111		0.111
	458.00	459.50	D009641	1.50	0.273		0.273
	459.50	461.00	D009642	1.50	<0.005		0.001
	461.00	462.50	D009643	1.50	<0.005		0.001
	462.50	464.00	D009644	1.50	<0.005		0.001
	464.00	465.50	D009645	1.50	0.134		0.134
	465.50	467.00	D009646	1.50	0.029		0.029
467.00	Fin du sondage Nombre d'échantillons : 310 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 464.30						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.00	8.50	D009297	D009296	1.50	0.009	0.009
20.50	22.00	D009307	F2	1.50	8.330	8.330
34.00	35.50	D009317	D009316	1.50	0.013	0.013
40.00	41.50	D009322	M1	1.50	0.010	0.010
46.00	47.50	D009327	G2	1.50	4.020	4.020
59.50	61.00	D009337	D009336	1.50	0.023	0.023
73.00	74.50	D009347	H	1.50	1.010	1.010
86.50	88.00	D009357	D009356	1.50	<0.005	0.001
92.50	92.50	D009362	M1	0.00	<0.005	0.001
98.50	100.00	D009367	A3	1.50	0.590	0.590
111.50	113.00	D009377	D009376	1.50	0.008	0.008
125.00	126.50	D009387	B4	1.50	2.550	2.550
138.50	140.00	D009397	D009396	1.50	0.072	0.072
144.50	146.00	D009402	M1	1.50	<0.005	0.001
150.50	152.00	D009407	C4	1.50	1.320	1.320
164.00	165.50	D009417	D009416	1.50	<0.005	0.001
177.50	177.50	D009427	D2	0.00	0.819	0.819
191.00	192.50	D009437	D009436	1.50	0.037	0.037
197.00	198.50	D009442	M1	1.50	<0.005	0.001
203.00	204.50	D009447	M	1.50	3.140	3.140
216.50	218.00	D009457	D009456	1.50	<0.005	0.001
230.00	231.50	D009467	G2	1.50	3.960	3.960
243.50	245.00	D009477	D009476	1.50	<0.005	0.001
249.50	251.00	D009482	M1	1.50	<0.005	0.001
255.50	257.00	D009487	H	1.50	0.988	0.988
269.00	270.50	D009497	D009496	1.50	0.147	0.147
275.00	276.50	D009502	M1	1.50	<0.005	0.001
281.00	282.50	D009507	A3	1.50	0.576	0.576
294.50	296.00	D009517	D009516	1.50	<0.005	0.001
308.00	309.50	D009527	H	1.50	0.933	0.933
321.50	323.00	D009537	D009536	1.50	0.016	0.016
327.50	329.00	D009542	M1	1.50	<0.005	0.001
333.50	335.00	D009547	D009546	1.50	0.100	0.100

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
347.00	348.50	D009557	D009556	1.50	<0.005	0.001
360.50	362.00	D009567	B4	1.50	2.590	2.590
374.00	375.50	D009577	D009576	1.50	0.005	0.005
380.00	381.50	D009582	M1	1.50	<0.005	0.001
386.00	387.50	D009587	M	1.50	2.670	2.670
399.50	401.00	D009597	D009596	1.50	<0.005	0.001
413.00	414.50	D009607	H	1.50	1.020	1.020
426.50	428.00	D009617	D009616	1.50	<0.005	0.001
432.50	434.00	D009622	M1	1.50	<0.005	0.001
438.50	440.00	D009627	D2	1.50	0.843	0.843
452.00	453.50	D009637	D009636	1.50	<0.005	0.001
465.50	467.00	D009647	A3	1.50	0.601	0.601

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-171**

Titre minier :

Section :                      630700

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy Gbaguidi

Lot :

Du :                      2010-04-29

Date de description :

Au :                      2010-05-04

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      448.30 m

Est	630 700.0
Nord	5 374 364.0
Élévation	308.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	357.00°	-60.20°	Oui
Reflex	15.00	3.10°	-60.00°	Non
Reflex	25.00	2.80°	-60.10°	Non
Reflex	35.00	2.90°	-60.10°	Non
Reflex	45.00	4.10°	-60.10°	Non
Reflex	55.00	3.20°	-60.10°	Non
Reflex	65.00	2.40°	-60.00°	Non
Reflex	75.00	2.40°	-60.30°	Non
Reflex	85.00	3.40°	-60.40°	Non
Reflex	95.00	5.80°	-60.50°	Non
Reflex	105.00	5.70°	-60.30°	Non
Reflex	115.00	5.40°	-60.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	125.00	5.90°	-59.70°	Non
Reflex	135.00	4.40°	-59.70°	Non
Reflex	145.00	3.80°	-59.70°	Non
Reflex	155.00	1.20°	-59.70°	Oui
Reflex	165.00	5.30°	-59.70°	Non
Reflex	175.00	5.60°	-59.60°	Non
Reflex	185.00	6.00°	-59.60°	Non
Reflex	195.00	5.80°	-59.60°	Non
Reflex	205.00	4.90°	-59.50°	Non
Reflex	215.00	3.10°	-58.80°	Non
Reflex	225.00	2.30°	-58.50°	Non
Reflex	235.00	1.50°	-57.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	245.00	3.10°	-57.70°	Non					
Reflex	255.00	3.90°	-57.90°	Non					
Reflex	265.00	2.70°	-57.80°	Non					
Reflex	275.00	5.00°	-57.60°	Oui					
Reflex	285.00	3.80°	-57.70°	Non					
Reflex	295.00	4.10°	-57.60°	Non					
Reflex	305.00	1.30°	-57.50°	Oui					
Reflex	315.00	4.00°	-57.50°	Non					
Reflex	325.00	3.90°	-57.60°	Non					
Reflex	335.00	3.80°	-57.30°	Non					
Reflex	345.00	3.40°	-57.10°	Non					
Reflex	355.00	3.80°	-57.20°	Non					
Reflex	365.00	5.20°	-57.20°	Non					
Reflex	375.00	6.00°	-57.20°	Non					
Reflex	385.00	9.00°	-57.30°	Oui					
Reflex	395.00	5.80°	-57.10°	Non					
Reflex	405.00	2.90°	-57.00°	Oui					
Reflex	415.00	5.80°	-57.00°	Non					
Reflex	425.00	5.50°	-56.90°	Non					
Reflex	435.00	6.00°	-56.70°	Non					
Reflex	445.00	7.00°	-56.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT						
		<b>Mort-terrain</b>						
3.00	448.30	SY	3.00	4.50	D013860	1.50	0.069	0.069
		<b>Syénite</b>	4.50	6.00	D013861	1.50	0.028	0.028
			6.00	7.50	D013862	1.50	0.116	0.116
			7.50	9.00	D013863	1.50	0.010	0.010
			9.00	10.50	D013864	1.50	0.005	0.005
			10.50	12.00	D013866	1.50	0.059	0.059
			12.00	13.50	D013867	1.50	0.090	0.090
			13.50	15.00	D013868	1.50	<0.005	0.001
			15.00	16.50	D013869	1.50	0.053	0.053
			16.50	18.00	D013870	1.50	0.669	0.669
			18.00	19.50	D013871	1.50	0.049	0.049
			19.50	21.00	D013872	1.50	0.061	0.061
			21.00	22.50	D013873	1.50	0.013	0.013
			22.50	24.00	D013874	1.50	0.048	0.048
			24.00	25.00	D013876	1.00	0.026	0.026
			25.00	26.00	D013877	1.00	0.005	0.005
			26.00	27.30	D013878	1.30	0.039	0.039
			27.30	29.00	D013879	1.70	0.089	0.089
			29.00	30.50	D013881	1.50	<0.005	0.001
			30.50	32.00	D013882	1.50	0.262	0.262
			32.00	33.50	D013883	1.50	0.006	0.006
			33.50	35.00	D013884	1.50	0.006	0.006
			35.00	36.50	D013886	1.50	0.050	0.050
			36.50	38.00	D013887	1.50	<0.005	0.001
			38.00	39.50	D013888	1.50	<0.005	0.001
			39.50	41.00	D013889	1.50	<0.005	0.001
			41.00	42.50	D013890	1.50	<0.005	0.001
			42.50	44.00	D013891	1.50	<0.005	0.001
			44.00	45.50	D013892	1.50	0.402	0.402
			45.50	47.00	D013893	1.50	0.093	0.093
			47.00	48.50	D013894	1.50	0.009	0.009
			48.50	50.00	D013896	1.50	0.093	0.093



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.50	D013897	1.50	0.042		0.042
	51.50	53.00	D013898	1.50	0.012		0.012
	53.00	54.50	D013899	1.50	<0.005		0.001
	54.50	56.00	D013900	1.50	<0.005		0.001
	56.00	57.50	D013901	1.50	0.008		0.008
	57.50	59.00	D013902	1.50	0.169		0.169
	59.00	60.50	D013903	1.50	0.375		0.375
	60.50	62.00	D013904	1.50	<0.005		0.001
	62.00	63.50	D013906	1.50	<0.005		0.001
	63.50	65.00	D013907	1.50	<0.005		0.001
	65.00	66.50	D013908	1.50	0.008		0.008
	66.50	68.00	D013909	1.50	<0.005		0.001
	68.00	69.50	D013910	1.50	0.005		0.005
	69.50	71.00	D013911	1.50	<0.005		0.001
	71.00	72.50	D013912	1.50	<0.005		0.001
	72.50	74.00	D013913	1.50	<0.005		0.001
	74.00	75.50	D013914	1.50	<0.005		0.001
	75.50	77.00	D013916	1.50	0.045		0.045
	77.00	78.00	D013917	1.00	0.045		0.045
	78.00	79.00	D013918	1.00	0.034		0.034
	79.00	80.60	D013919	1.60	0.015		0.015
	80.60	82.00	D013921	1.40	<0.005		0.001
	82.00	83.50	D013922	1.50	<0.005		0.001
	83.50	85.00	D013923	1.50	0.008		0.008
	85.00	86.50	D013924	1.50	<0.005		0.001
	86.50	88.00	D013926	1.50	<0.005		0.001
	88.00	89.50	D013927	1.50	0.185		0.185
	89.50	91.00	D013928	1.50	<0.005		0.001
	91.00	92.30	D013929	1.30	<0.005		0.001
	92.30	94.00	D013930	1.70	<0.005		0.001
	94.00	95.50	D013931	1.50	<0.005		0.001
	95.50	97.00	D013932	1.50	<0.005		0.001
	97.00	98.00	D013933	1.00	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.00	99.50	D013934	1.50	0.010		0.010
	99.50	101.00	D013936	1.50	0.005		0.005
	101.00	102.00	D013937	1.00	0.010		0.010
	102.00	103.50	D013938	1.50	0.007		0.007
	103.50	105.00	D013939	1.50	<0.005		0.001
	105.00	106.50	D013940	1.50	0.063		0.063
	106.50	108.00	D013941	1.50	<0.005		0.001
	108.00	109.50	D013942	1.50	0.546		0.546
	109.50	111.00	D013943	1.50	<0.005		0.001
	111.00	112.00	D013944	1.00	0.776		0.776
	112.00	113.00	D013946	1.00	5.600		5.600
	113.00	114.50	D013947	1.50	0.021		0.021
	114.50	116.00	D013948	1.50	0.258		0.258
	116.00	117.50	D013949	1.50	0.018		0.018
	117.50	118.70	D013950	1.20	0.081		0.081
	118.70	120.00	D013951	1.30	<0.005		0.001
	120.00	121.50	D013952	1.50	<0.005		0.001
	121.50	123.00	D013953	1.50	<0.005		0.001
	123.00	124.00	D013954	1.00	<0.005		0.001
	124.00	125.00	D013956	1.00	<0.005		0.001
	125.00	126.30	D013957	1.30	0.007		0.007
	126.30	128.00	D013958	1.70	0.025		0.025
	128.00	129.50	D013959	1.50	0.037		0.037
	129.50	131.00	D013961	1.50	<0.005		0.001
	131.00	132.50	D013962	1.50	<0.005		0.001
	132.50	134.00	D013963	1.50	<0.005		0.001
	134.00	135.50	D013964	1.50	<0.005		0.001
	135.50	137.00	D013966	1.50	<0.005		0.001
	137.00	138.50	D013967	1.50	<0.005		0.001
	138.50	140.00	D013968	1.50	0.014		0.014
	140.00	141.50	D013969	1.50	<0.005		0.001
	141.50	143.00	D013970	1.50	<0.005		0.001
	143.00	144.50	D013971	1.50	0.056		0.056

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	144.50	146.00	D013972	1.50	0.005		0.005
	146.00	147.50	D013973	1.50	0.005		0.005
	147.50	149.00	D013974	1.50	0.055		0.055
	149.00	150.50	D013976	1.50	0.005		0.005
	150.50	152.00	D013977	1.50	<0.005		0.001
	152.00	153.50	D013978	1.50	0.006		0.006
	153.50	155.00	D013979	1.50	0.137		0.137
	155.00	156.50	D013980	1.50	0.049		0.049
	156.50	158.00	D013981	1.50	0.014		0.014
	158.00	159.50	D013982	1.50	0.007		0.007
	159.50	161.00	D013983	1.50	0.081		0.081
	161.00	162.50	D013984	1.50	0.017		0.017
	162.50	164.00	D013986	1.50	0.310		0.310
	164.00	165.50	D013987	1.50	0.071		0.071
	165.50	167.00	D013988	1.50	0.005		0.005
	167.00	168.50	D013989	1.50	0.017		0.017
	168.50	170.00	D013990	1.50	0.203		0.203
	170.00	171.50	D013991	1.50	0.007		0.007
	171.50	173.00	D013992	1.50	0.005		0.005
	173.00	174.50	D013993	1.50	<0.005		0.001
	174.50	176.00	D013994	1.50	0.006		0.006
	176.00	177.50	D013996	1.50	<0.005		0.001
	177.50	178.80	D013997	1.30	<0.005		0.001
	178.80	180.50	D013998	1.70	0.033		0.033
	180.50	182.00	D013999	1.50	0.008		0.008
	182.00	183.50	D014001	1.50	0.009		0.009
	183.50	185.00	D014002	1.50	0.009		0.009
	185.00	186.00	D014003	1.00	0.007		0.007
	186.00	187.50	D014004	1.50	0.839		0.839
	187.50	189.00	D014006	1.50	0.039		0.039
	189.00	190.30	D014007	1.30	0.028		0.028
	190.30	192.00	D014008	1.70	0.377		0.377
	192.00	193.50	D014009	1.50	0.772		0.772

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	193.50	195.00	D014010	1.50	0.013		0.013
	195.00	196.50	D014011	1.50	0.015		0.015
	196.50	198.00	D014012	1.50	0.081		0.081
	198.00	199.50	D014013	1.50	0.032		0.032
	199.50	201.00	D014014	1.50	<0.005		0.001
	201.00	202.00	D014016	1.00	0.005		0.005
	202.00	203.00	D014017	1.00	<0.005		0.001
	203.00	204.50	D014018	1.50	0.009		0.009
	204.50	206.00	D014019	1.50	<0.005		0.001
	206.00	207.50	D014020	1.50	<0.005		0.001
	207.50	209.00	D014021	1.50	0.009		0.009
	209.00	210.50	D014022	1.50	0.008		0.008
	210.50	212.00	D014023	1.50	<0.005		0.001
	212.00	213.00	D014024	1.00	0.005		0.005
	213.00	214.50	D014026	1.50	0.013		0.013
	214.50	216.00	D014027	1.50	0.108		0.108
	216.00	217.50	D014028	1.50	0.151		0.151
	217.50	219.00	D014029	1.50	0.375		0.375
	219.00	220.50	D014030	1.50	0.037		0.037
	220.50	222.00	D014031	1.50	0.053		0.053
	222.00	223.50	D014032	1.50	0.008		0.008
	223.50	225.00	D014033	1.50	0.024		0.024
	225.00	226.50	D014034	1.50	0.056		0.056
	226.50	228.00	D014036	1.50	0.013		0.013
	228.00	229.50	D014037	1.50	0.010		0.010
	229.50	231.00	D014038	1.50	0.017		0.017
	231.00	232.50	D014039	1.50	0.030		0.030
	232.50	234.00	D014040	1.50	<0.005		0.001
	234.00	235.50	D014041	1.50	0.429		0.429
	235.50	237.00	D014042	1.50	0.014		0.014
	237.00	238.50	D014043	1.50	<0.005		0.001
	238.50	240.00	D014044	1.50	0.005		0.005
	240.00	241.50	D014046	1.50	0.045		0.045

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	241.50	243.00	D014047	1.50	0.009		0.009
	243.00	244.50	D014048	1.50	0.013		0.013
	244.50	246.00	D014049	1.50	0.015		0.015
	246.00	247.50	D014050	1.50	0.018		0.018
	247.50	249.00	D014051	1.50	0.005		0.005
	249.00	250.50	D014052	1.50	0.008		0.008
	250.50	252.00	D014053	1.50	0.008		0.008
	252.00	253.50	D014054	1.50	0.007		0.007
	253.50	255.00	D014056	1.50	<0.005		0.001
	255.00	256.50	D014057	1.50	0.018		0.018
	256.50	258.00	D014058	1.50	0.010		0.010
	258.00	259.50	D014059	1.50	0.034		0.034
	259.50	261.00	D014060	1.50	0.175		0.175
	261.00	262.50	D014061	1.50	0.008		0.008
	262.50	264.00	D014062	1.50	0.839		0.839
	264.00	265.50	D014063	1.50	0.050		0.050
	265.50	267.00	D014064	1.50	0.013		0.013
	267.00	268.50	D014066	1.50	0.150		0.150
	268.50	270.00	D014067	1.50	0.028		0.028
	270.00	271.50	D014068	1.50	0.021		0.021
	271.50	273.00	D014069	1.50	0.403		0.403
	273.00	274.50	D014070	1.50	0.044		0.044
	274.50	276.00	D014071	1.50	0.071		0.071
	276.00	277.50	D014072	1.50	0.461		0.461
	277.50	279.00	D014073	1.50	0.157		0.157
	279.00	280.50	D014074	1.50	0.171		0.171
	280.50	282.00	D014076	1.50	0.356		0.356
	282.00	283.50	D014077	1.50	0.759		0.759
	283.50	285.00	D014078	1.50	0.392		0.392
	285.00	286.50	D014079	1.50	0.156		0.156
	286.50	288.00	D014081	1.50	0.010		0.010
	288.00	289.50	D014082	1.50	0.005		0.005
	289.50	291.00	D014083	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	291.00	292.50	D014084	1.50	0.038		0.038
	292.50	294.00	D014086	1.50	0.187		0.187
	294.00	295.50	D014087	1.50	0.090		0.090
	295.50	297.00	D014088	1.50	0.046		0.046
	297.00	298.50	D014089	1.50	0.023		0.023
	298.50	300.00	D014090	1.50	0.012		0.012
	300.00	301.50	D014091	1.50	0.018		0.018
	301.50	303.00	D014092	1.50	<0.005		0.001
	303.00	304.50	D014093	1.50	<0.005		0.001
	304.50	306.00	D014094	1.50	0.006		0.006
	306.00	307.50	D014096	1.50	0.005		0.005
	307.50	309.00	D014097	1.50	<0.005		0.001
	309.00	310.50	D014098	1.50	<0.005		0.001
	310.50	312.00	D014099	1.50	0.044		0.044
	312.00	313.00	D014100	1.00	0.053		0.053
	313.00	314.50	D014101	1.50	0.057		0.057
	314.50	316.00	D014102	1.50	0.016		0.016
	316.00	317.50	D014103	1.50	0.043		0.043
	317.50	319.00	D014104	1.50	<0.005		0.001
	319.00	320.50	D014106	1.50	<0.005		0.001
	320.50	322.00	D014107	1.50	0.008		0.008
	322.00	323.50	D014108	1.50	0.062		0.062
	323.50	325.00	D014109	1.50	0.008		0.008
	325.00	326.50	D014110	1.50	<0.005		0.001
	326.50	328.00	D014111	1.50	0.084		0.084
	328.00	329.50	D014112	1.50	0.145		0.145
	329.50	331.00	D014113	1.50	0.006		0.006
	331.00	332.50	D014114	1.50	<0.005		0.001
	332.50	334.00	D014116	1.50	<0.005		0.001
	334.00	335.50	D014117	1.50	<0.005		0.001
	335.50	337.00	D014118	1.50	<0.005		0.001
	337.00	338.50	D014119	1.50	<0.005		0.001
	338.50	340.00	D014121	1.50	0.608		0.608

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	340.00	341.00	D014122	1.00	3.030		3.030
	341.00	342.50	D014123	1.50	0.281		0.281
	342.50	344.00	D014124	1.50	0.555		0.555
	344.00	345.50	D014126	1.50	<0.005		0.001
	345.50	347.00	D014127	1.50	<0.005		0.001
	347.00	348.50	D014128	1.50	0.005		0.005
	348.50	350.00	D014129	1.50	<0.005		0.001
	350.00	351.50	D014130	1.50	<0.005		0.001
	351.50	353.00	D014131	1.50	<0.005		0.001
	353.00	354.50	D014132	1.50	<0.005		0.001
	354.50	356.00	D014133	1.50	<0.005		0.001
	356.00	357.50	D014134	1.50	<0.005		0.001
	357.50	359.00	D014136	1.50	0.006		0.006
	359.00	360.50	D014137	1.50	0.005		0.005
	360.50	362.00	D014138	1.50	0.026		0.026
	362.00	363.50	D014139	1.50	0.022		0.022
	363.50	365.00	D014140	1.50	0.005		0.005
	365.00	366.50	D014141	1.50	0.010		0.010
	366.50	368.00	D014142	1.50	0.008		0.008
	368.00	369.50	D014143	1.50	0.021		0.021
	369.50	371.00	D014144	1.50	0.032		0.032
	371.00	372.50	D014146	1.50	<0.005		0.001
	372.50	374.00	D014147	1.50	0.020		0.020
	374.00	375.50	D014148	1.50	0.037		0.037
	375.50	377.00	D014149	1.50	0.597		0.597
	377.00	378.50	D014150	1.50	1.105		1.105
	378.50	380.00	D014151	1.50	0.005		0.005
	380.00	381.50	D014152	1.50	<0.005		0.001
	381.50	383.00	D014153	1.50	<0.005		0.001
	383.00	384.50	D014154	1.50	<0.005		0.001
	384.50	386.00	D014156	1.50	<0.005		0.001
	386.00	387.50	D014157	1.50	<0.005		0.001
	387.50	389.00	D014158	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	389.00	390.50	D014159	1.50	<0.005		0.001
	390.50	392.00	D014161	1.50	<0.005		0.001
	392.00	393.50	D014162	1.50	0.064		0.064
	393.50	395.00	D014163	1.50	<0.005		0.001
	395.00	396.50	D014164	1.50	0.008		0.008
	396.50	398.00	D014166	1.50	<0.005		0.001
	398.00	399.50	D014167	1.50	<0.005		0.001
	399.50	401.00	D014168	1.50	<0.005		0.001
	401.00	402.50	D014169	1.50	<0.005		0.001
	402.50	404.00	D014170	1.50	<0.005		0.001
	404.00	405.50	D014171	1.50	<0.005		0.001
	405.50	407.00	D014172	1.50	<0.005		0.001
	407.00	408.50	D014173	1.50	<0.005		0.001
	408.50	410.00	D014174	1.50	<0.005		0.001
	410.00	411.50	D014176	1.50	<0.005		0.001
	411.50	413.00	D014177	1.50	<0.005		0.001
	413.00	414.50	D014178	1.50	0.007		0.007
	414.50	416.00	D014179	1.50	<0.005		0.001
	416.00	417.50	D014180	1.50	<0.005		0.001
	417.50	419.00	D014181	1.50	0.019		0.019
	419.00	420.50	D014182	1.50	0.192		0.192
	420.50	422.00	D014183	1.50	0.220		0.220
	422.00	423.50	D014184	1.50	0.461		0.461
	423.50	425.00	D014186	1.50	0.011		0.011
	425.00	426.50	D014187	1.50	0.284		0.284
	426.50	428.00	D014188	1.50	0.065		0.065
	428.00	429.50	D014189	1.50	0.026		0.026
	429.50	431.00	D014190	1.50	0.035		0.035
	431.00	432.10	D014191	1.10	0.006		0.006
	432.10	433.80	D014192	1.70	0.010		0.010
	433.80	435.50	D014193	1.70	0.014		0.014
	435.50	437.00	D014194	1.50	0.006		0.006
	437.00	438.50	D014196	1.50	0.006		0.006



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	438.50	439.90	D014197	1.40	<0.005		0.001
	439.90	441.50	D014198	1.60	<0.005		0.001
	441.50	443.00	D014199	1.50	0.007		0.007
	443.00	444.50	D014200	1.50	0.035		0.035
	444.50	446.00	D014201	1.50	<0.005		0.001
	446.00	447.00	D014202	1.00	<0.005		0.001
	447.00	448.30	D014203	1.30	<0.005		0.001
<p>448.30 Fin du sondage            Nombre d'échantillons : 303            Nombre d'échantillons QAQC : 41            Longueur totale échantillonnée : 445.30</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.00	10.50	D013865	D013864	1.50	0.018	0.018
22.50	22.50	D013875	D2	0.00	0.868	0.868
27.30	27.30	D013880	M1	0.00	<0.005	0.001
33.50	35.00	D013885	D013884	1.50	0.006	0.006
47.00	47.00	D013895	G2	0.00	3.970	3.970
60.50	62.00	D013905	D013904	1.50	<0.005	0.001
74.00	74.00	D013915	H	0.00	1.010	1.010
79.00	79.00	D013920	M1	0.00	<0.005	0.001
85.00	86.50	D013925	D013924	1.50	<0.005	0.001
98.00	98.00	D013935	A3	0.00	0.588	0.588
111.00	112.00	D013945	D013944	1.00	0.821	0.821
123.00	123.00	D013955	B4	0.00	2.540	2.540
128.00	128.00	D013960	M1	0.00	0.005	0.005
134.00	135.50	D013965	D013964	1.50	<0.005	0.001
147.50	147.50	D013975	C4	0.00	1.350	1.350
161.00	162.50	D013985	D013984	1.50	0.007	0.007
174.50	174.50	D013995	D2	0.00	0.872	0.872
180.50	180.50	D014000	M1	0.00	<0.005	0.001
186.00	187.50	D014005	D014004	1.50	0.734	0.734
199.50	199.50	D014015	G2	0.00	4.050	4.050
212.00	213.00	D014025	D014024	1.00	0.008	0.008
225.00	225.00	D014035	H	0.00	0.986	0.986
238.50	240.00	D014045	D014044	1.50	<0.005	0.001
252.00	252.00	D014055	A3	0.00	0.609	0.609
265.50	267.00	D014065	D014064	1.50	0.013	0.013
279.00	279.00	D014075	B4	0.00	2.630	2.630
285.00	285.00	D014080	M1	0.00	<0.005	0.001
291.00	292.50	D014085	D014084	1.50	0.043	0.043
304.50	304.50	D014095	C4	0.00	1.275	1.275
317.50	319.00	D014105	D014104	1.50	<0.005	0.001
331.00	331.00	D014115	D2	0.00	0.891	0.891
337.00	337.00	D014120	M1	0.00	<0.005	0.001
342.50	344.00	D014125	D014124	1.50	0.561	0.561

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
356.00	356.00	D014135	G2	0.00	4.050	4.050
369.50	371.00	D014145	D014144	1.50	0.029	0.029
383.00	383.00	D014155	H	0.00	0.990	0.990
389.00	389.00	D014160	M1	0.00	<0.005	0.001
395.00	396.50	D014165	D014164	1.50	0.006	0.006
408.50	408.50	D014175	A3	0.00	0.597	0.597
422.00	423.50	D014185	D014184	1.50	0.472	0.472
435.50	435.50	D014195	B4	0.00	2.520	2.520

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-172**

Titre minier :

Section :                      631000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-04-25

Date de description :

Au :                      2010-05-02

Collet

UTM

Azimut :                0.00°

Plongée :              -60.00°

Longueur :            465.30 m

Est                      631 001.2

Nord                    5 374 249.0

Élévation              308.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	0.00°	0.00°	Non
Reflex	3.00	1.10°	-60.20°	Non
Reflex	6.00	1.30°	-60.20°	Non
Reflex	9.00	1.70°	-60.10°	Non
Reflex	12.00	1.50°	-60.10°	Non
Reflex	15.00	1.50°	-60.00°	Non
Reflex	18.00	1.60°	-60.00°	Non
Reflex	21.00	1.60°	-60.10°	Non
Reflex	24.00	1.60°	-60.00°	Non
Reflex	27.00	1.60°	-59.80°	Non
Reflex	30.00	1.70°	-59.70°	Non
Reflex	33.00	1.60°	-59.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	1.40°	-59.50°	Non
Reflex	39.00	1.50°	-59.40°	Non
Reflex	42.00	1.40°	-59.30°	Non
Reflex	45.00	1.30°	-59.30°	Non
Reflex	48.00	1.30°	-59.30°	Non
Reflex	51.00	1.30°	-59.30°	Non
Reflex	54.00	1.40°	-59.40°	Non
Reflex	57.00	1.50°	-59.30°	Non
Reflex	60.00	1.60°	-59.40°	Non
Reflex	63.00	1.80°	-59.40°	Non
Reflex	66.00	2.20°	-59.40°	Non
Reflex	69.00	2.60°	-59.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	72.00	2.80°	-59.50°	Non	Reflex	171.00	6.00°	-59.40°	Non
Reflex	75.00	3.20°	-59.50°	Non	Reflex	174.00	7.00°	-59.30°	Non
Reflex	78.00	3.40°	-59.50°	Non	Reflex	177.00	6.20°	-59.30°	Non
Reflex	81.00	3.20°	-59.60°	Non	Reflex	180.00	6.30°	-59.30°	Non
Reflex	84.00	3.40°	-59.50°	Non	Reflex	183.00	6.30°	-59.20°	Non
Reflex	87.00	3.50°	-59.50°	Non	Reflex	186.00	6.00°	-59.10°	Non
Reflex	90.00	3.60°	-59.60°	Non	Reflex	189.00	6.10°	-59.10°	Non
Reflex	93.00	3.60°	-59.50°	Non	Reflex	192.00	6.30°	-59.00°	Non
Reflex	96.00	3.70°	-59.40°	Non	Reflex	195.00	6.40°	-59.00°	Non
Reflex	99.00	3.90°	-59.30°	Non	Reflex	198.00	6.30°	-58.90°	Non
Reflex	102.00	4.00°	-59.30°	Non	Reflex	201.00	6.50°	-58.90°	Non
Reflex	105.00	4.20°	-59.40°	Non	Reflex	204.00	6.50°	-58.80°	Non
Reflex	108.00	4.30°	-59.40°	Non	Reflex	207.00	6.90°	-58.80°	Non
Reflex	111.00	4.40°	-59.40°	Non	Reflex	210.00	6.70°	-58.80°	Non
Reflex	114.00	4.60°	-59.40°	Non	Reflex	213.00	6.50°	-58.70°	Non
Reflex	117.00	4.50°	-59.40°	Non	Reflex	216.00	6.80°	-58.70°	Non
Reflex	120.00	3.70°	-59.40°	Oui	Reflex	219.00	6.80°	-58.70°	Non
Reflex	123.00	5.50°	-59.40°	Non	Reflex	222.00	6.50°	-58.70°	Non
Reflex	126.00	5.30°	-59.40°	Non	Reflex	225.00	6.60°	-58.70°	Non
Reflex	129.00	5.70°	-59.40°	Non	Reflex	228.00	6.50°	-58.70°	Non
Reflex	132.00	5.00°	-59.40°	Non	Reflex	231.00	6.60°	-58.70°	Non
Reflex	135.00	5.30°	-59.40°	Non	Reflex	234.00	6.50°	-58.70°	Non
Reflex	138.00	5.40°	-59.40°	Non	Reflex	237.00	6.20°	-58.70°	Non
Reflex	141.00	5.50°	-59.40°	Non	Reflex	240.00	6.60°	-58.70°	Non
Reflex	144.00	5.40°	-59.40°	Non	Reflex	243.00	6.50°	-58.70°	Non
Reflex	147.00	5.70°	-59.40°	Non	Reflex	246.00	6.10°	-58.70°	Non
Reflex	150.00	6.10°	-59.40°	Non	Reflex	249.00	5.70°	-58.70°	Non
Reflex	153.00	5.60°	-59.30°	Non	Reflex	252.00	7.20°	-58.70°	Non
Reflex	156.00	5.50°	-59.30°	Non	Reflex	255.00	8.90°	-58.70°	Non
Reflex	159.00	5.70°	-59.30°	Non	Reflex	258.00	11.30°	-58.70°	Oui
Reflex	162.00	5.80°	-59.30°	Non	Reflex	261.00	9.10°	-58.70°	Non
Reflex	165.00	5.90°	-59.40°	Non	Reflex	264.00	9.60°	-58.70°	Non
Reflex	168.00	5.90°	-59.40°	Non	Reflex	267.00	10.70°	-58.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	270.00	11.10°	-58.60°	Non	Reflex	369.00	13.40°	-58.00°	Non
Reflex	273.00	12.00°	-58.60°	Non	Reflex	372.00	9.80°	-58.00°	Non
Reflex	276.00	13.30°	-58.50°	Non	Reflex	375.00	10.70°	-58.00°	Non
Reflex	279.00	13.50°	-58.50°	Non	Reflex	378.00	15.50°	-57.90°	Oui
Reflex	282.00	11.20°	-58.50°	Non	Reflex	381.00	13.20°	-57.90°	Non
Reflex	285.00	10.60°	-58.40°	Non	Reflex	384.00	14.90°	-57.90°	Non
Reflex	288.00	9.40°	-58.40°	Non	Reflex	387.00	15.40°	-57.90°	Non
Reflex	291.00	10.50°	-58.40°	Non	Reflex	390.00	14.80°	-57.80°	Non
Reflex	294.00	10.70°	-58.40°	Non	Reflex	393.00	14.70°	-57.80°	Non
Reflex	297.00	11.00°	-58.40°	Non	Reflex	396.00	13.80°	-57.70°	Non
Reflex	300.00	11.50°	-58.40°	Non	Reflex	399.00	16.00°	-57.70°	Oui
Reflex	303.00	11.30°	-58.40°	Non	Reflex	402.00	14.90°	-57.50°	Non
Reflex	306.00	12.20°	-58.40°	Oui	Reflex	405.00	17.80°	-57.40°	Oui
Reflex	309.00	10.40°	-58.40°	Non	Reflex	408.00	14.70°	-57.40°	Non
Reflex	312.00	13.80°	-58.40°	Non	Reflex	411.00	15.70°	-57.40°	Non
Reflex	315.00	13.80°	-58.40°	Non	Reflex	414.00	14.30°	-57.30°	Non
Reflex	318.00	13.50°	-58.40°	Non	Reflex	417.00	15.80°	-57.30°	Non
Reflex	321.00	14.30°	-58.40°	Non	Reflex	420.00	17.30°	-57.20°	Oui
Reflex	324.00	13.50°	-58.50°	Non	Reflex	423.00	14.30°	-57.10°	Non
Reflex	327.00	13.80°	-58.40°	Non	Reflex	426.00	14.30°	-57.10°	Non
Reflex	330.00	13.40°	-58.40°	Non	Reflex	429.00	14.20°	-57.00°	Non
Reflex	333.00	12.80°	-58.40°	Non	Reflex	432.00	15.20°	-57.00°	Non
Reflex	336.00	13.60°	-58.30°	Non	Reflex	435.00	15.70°	-56.90°	Non
Reflex	339.00	14.10°	-58.20°	Non	Reflex	438.00	17.00°	-56.90°	Non
Reflex	342.00	15.60°	-58.20°	Oui	Reflex	441.00	17.80°	-56.90°	Non
Reflex	345.00	14.50°	-58.20°	Non	Reflex	444.00	17.90°	-56.90°	Non
Reflex	348.00	14.90°	-58.20°	Non	Reflex	447.00	16.00°	-56.90°	Non
Reflex	351.00	13.70°	-58.10°	Non	Reflex	450.00	15.10°	-56.90°	Non
Reflex	354.00	8.80°	-58.10°	Non	Reflex	453.00	16.90°	-56.90°	Non
Reflex	357.00	8.70°	-58.00°	Non	Reflex	456.00	16.00°	-56.90°	Non
Reflex	360.00	9.80°	-58.00°	Non	Reflex	459.00	17.20°	-56.80°	Non
Reflex	363.00	12.00°	-58.00°	Non	Reflex	462.00	16.70°	-56.80°	Non
Reflex	366.00	14.60°	-58.00°	Non	Reflex	465.00	16.60°	-56.70°	Non

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.60	MT						
		<b>Mort-terrain</b>						
2.60	10.00	BA; FIN; AMY	2.60	4.00	D009648	1.40	0.009	0.009
		<b>Basalte; Grains fins; Amygdalaire</b>	4.00	5.50	D009649	1.50	<0.005	0.001
		Basalte à grains fins et amygdalaire.	5.50	7.00	D009650	1.50	<0.005	0.001
			7.00	8.50	D009651	1.50	<0.005	0.001
			8.50	10.00	D009652	1.50	<0.005	0.001
10.00	21.00	SY; PT; FIN	10.00	11.50	D009653	1.50	0.059	0.059
		<b>Syénite 45°; Porphyre trachytique; Grains fins</b>	11.50	13.00	D009654	1.50	0.013	0.013
		Syénite, à grains fins, à porphyre trachytique avec phénocristaux Xmm	13.00	14.50	D009655	1.50	0.011	0.011
		à tendance allongé et ± 35° ac.	14.50	16.00	D009656	1.50	<0.005	0.001
			16.00	17.50	D009658	1.50	<0.005	0.001
			17.50	19.00	D009659	1.50	0.005	0.005
			19.00	20.00	D009660	1.00	<0.005	0.001
			20.00	21.00	D009661	1.00	0.261	0.261
21.00	53.00	BA; FIN; AMY	21.00	22.50	D009663	1.50	2.600	2.600
		<b>Basalte; Grains fins; Amygdalaire</b>	22.50	24.00	D009664	1.50	0.712	0.712
		Bsalte à grains fins et amygdalaire.						
23.00	28.00	FRC	24.00	25.50	D009665	1.50	0.007	0.007
		<b>Fracturé</b>	25.50	27.00	D009666	1.50	0.011	0.011
		Zone fracturée et oxydée.	27.00	28.50	D009668	1.50	0.009	0.009
			28.50	30.00	D009669	1.50	0.006	0.006
			30.00	31.50	D009670	1.50	<0.005	0.001
			31.50	33.00	D009671	1.50	<0.005	0.001
			33.00	34.50	D009672	1.50	<0.005	0.001
			34.50	36.00	D009673	1.50	<0.005	0.001
			36.00	37.50	D009674	1.50	<0.005	0.001
			37.50	39.00	D009675	1.50	0.011	0.011
			39.00	40.50	D009676	1.50	<0.005	0.001
			40.50	42.00	D009678	1.50	<0.005	0.001
			42.00	43.50	D009679	1.50	<0.005	0.001
			43.50	45.00	D009680	1.50	<0.005	0.001
			45.00	46.50	D009681	1.50	<0.005	0.001
			46.50	48.00	D009682	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
53.00	62.80	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite à grains fins et porphyrique.	48.00	49.50	D009683	1.50	<0.005		0.001
			49.50	51.00	D009684	1.50	0.005		0.005
			51.00	52.00	D009685	1.00	0.008		0.008
			52.00	53.00	D009686	1.00	1.505		1.505
			53.00	54.50	D009688	1.50	0.018		0.018
			54.50	56.00	D009689	1.50	1.535		1.535
			56.00	57.50	D009690	1.50	0.346		0.346
			57.50	59.00	D009691	1.50	0.074		0.074
			59.00	60.50	D009692	1.50	0.131		0.131
			60.50	62.00	D009693	1.50	<0.005		0.001
			62.80	110.50	BA; FIN; AMY <b>Basalte; Grains fins; Amygdalaire</b> Basalte, à grains fins, amygdalaire.	62.00	62.80	D009694	0.80
62.80	64.00	D009695				1.20	0.138		0.138
64.00	65.50	D009696				1.50	<0.005		0.001
65.50	67.00	D009698				1.50	0.521		0.521
67.00	68.50	D009699				1.50	0.005		0.005
68.50	70.00	D009700				1.50	0.005		0.005
70.00	71.50	D009701				1.50	0.008		0.008
71.50	73.00	D009703				1.50	0.258		0.258
73.00	74.50	D009704				1.50	0.005		0.005
74.50	76.00	D009705				1.50	0.008		0.008
76.00	77.50	D009706				1.50	0.010		0.010
77.50	79.00	D009708				1.50	0.006		0.006
79.00	80.50	D009709				1.50	<0.005		0.001
80.50	82.00	D009710				1.50	<0.005		0.001
82.00	83.50	D009711				1.50	<0.005		0.001
83.50	85.00	D009712				1.50	<0.005		0.001
85.00	86.50	D009713				1.50	<0.005		0.001
86.50	88.00	D009714				1.50	<0.005		0.001
88.00	89.50	D009715				1.50	0.013		0.013
89.50	91.00	D009716				1.50	<0.005		0.001
91.00	92.50	D009718	1.50	0.006		0.006			
92.50	94.00	D009719	1.50	0.248		0.248			
94.00	95.50	D009720	1.50	0.007		0.007			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
110.50	176.00	SY; FIN; POR <b>Syénite 65°; Grains fins; Porphyrique</b> Syénite, à grains fins à moyens, porphyrique avec phénocristaux Xmm à Xcm.	95.50	97.00	D009721	1.50	0.005		0.005
			97.00	98.50	D009722	1.50	0.119		0.119
			98.50	100.00	D009723	1.50	<0.005		0.001
			100.00	101.50	D009724	1.50	<0.005		0.001
			101.50	103.00	D009725	1.50	0.124		0.124
			103.00	104.50	D009726	1.50	0.362		0.362
			104.50	106.00	D009728	1.50	0.013		0.013
			106.00	107.70	D009729	1.70	<0.005		0.001
			107.70	109.00	D009730	1.30	0.755		0.755
			109.00	110.50	D009731	1.50	2.670		2.670
			110.50	112.00	D009732	1.50	0.560		0.560
			112.00	113.50	D009733	1.50	0.005		0.005
			113.50	115.00	D009734	1.50	0.019		0.019
			115.00	116.50	D009735	1.50	0.009		0.009
			116.50	118.00	D009736	1.50	<0.005		0.001
			118.00	119.50	D009738	1.50	0.063		0.063
			119.50	121.00	D009739	1.50	0.014		0.014
			121.00	122.50	D009740	1.50	0.030		0.030
			122.50	124.00	D009741	1.50	0.016		0.016
			124.00	125.50	D009743	1.50	0.016		0.016
			125.50	127.00	D009744	1.50	0.009		0.009
			127.00	128.50	D009745	1.50	0.008		0.008
			128.50	130.00	D009746	1.50	0.027		0.027
			130.00	131.50	D009748	1.50	0.011		0.011
			131.50	133.00	D009749	1.50	0.011		0.011
			133.00	134.50	D009750	1.50	0.010		0.010
			134.50	136.00	D009751	1.50	<0.005		0.001
			136.00	137.50	D009752	1.50	<0.005		0.001
137.50	139.00	D009753	1.50	0.134		0.134			
139.00	140.50	D009754	1.50	0.134		0.134			
140.50	142.00	D009755	1.50	0.048		0.048			
142.00	143.50	D009756	1.50	0.008		0.008			
143.50	145.00	D009758	1.50	0.073		0.073			

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	145.00	146.50	D009759	1.50	0.040		0.040	
	146.50	148.00	D009760	1.50	0.119		0.119	
	148.00	149.50	D009761	1.50	0.040		0.040	
	149.50	151.00	D009762	1.50	0.058		0.058	
	151.00	152.50	D009763	1.50	0.027		0.027	
	152.50	154.00	D009764	1.50	0.054		0.054	
	154.00	155.50	D009765	1.50	0.011		0.011	
	155.50	157.00	D009766	1.50	0.011		0.011	
	157.00	158.50	D009768	1.50	0.007		0.007	
	158.50	160.00	D009769	1.50	0.028		0.028	
	160.00	161.50	D009770	1.50	0.022		0.022	
	161.50	163.00	D009771	1.50	0.279		0.279	
	163.00	164.50	D009772	1.50	0.186		0.186	
	164.50	166.00	D009773	1.50	0.295		0.295	
	166.00	167.50	D009774	1.50	1.035		1.035	
	167.50	169.00	D009775	1.50	0.039		0.039	
	169.00	170.50	D009776	1.50	0.123		0.123	
	170.50	172.00	D009778	1.50	0.092		0.092	
	172.00	173.50	D009779	1.50	0.449		0.449	
	173.50	175.00	D009780	1.50	0.043		0.043	
	175.00	176.00	D009781	1.00	0.005		0.005	
176.00	225.60	BA; FIN; AMY	176.00	177.50	D009783	1.50	0.009	0.009
		<b>Basalte 45°; Grains fins; Amygdalaire</b>	177.50	179.00	D009784	1.50	0.006	0.006
		Basalte, à grains fins avec passage amygdalaire.	179.00	180.50	D009785	1.50	0.007	0.007
			180.50	182.00	D009786	1.50	0.014	0.014
			182.00	183.50	D009788	1.50	0.014	0.014
			183.50	185.00	D009789	1.50	0.013	0.013
			185.00	186.50	D009790	1.50	0.010	0.010
			186.50	188.00	D009791	1.50	0.013	0.013
			188.00	189.50	D009792	1.50	0.620	0.620
			189.50	191.00	D009793	1.50	<0.005	0.001
			191.00	192.50	D009794	1.50	0.011	0.011
			192.50	194.00	D009795	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
202.00	203.00	BA; BRC <b>Basalte 35°; Brèche de coulée</b> Basalte bréchifié avec de fragments sub-anguleux à anguleux.	194.00	195.50	D009796	1.50	0.019		0.019
			195.50	197.00	D009798	1.50	0.023		0.023
			197.00	198.50	D009799	1.50	1.095		1.095
			198.50	200.00	D009800	1.50	0.007		0.007
			200.00	201.00	D009801	1.00	0.006		0.006
			201.00	202.00	D009802	1.00	0.018		0.018
			202.00	203.00	D009803	1.00	0.010		0.010
			203.00	204.50	D009804	1.50	0.698		0.698
			204.50	206.00	D009805	1.50	0.005		0.005
			206.00	207.50	D009806	1.50	<0.005		0.001
			207.50	209.00	D009808	1.50	0.095		0.095
			209.00	210.50	D009809	1.50	0.811		0.811
			210.50	212.00	D009810	1.50	<0.005		0.001
			212.00	213.50	D009811	1.50	<0.005		0.001
			213.50	215.00	D009812	1.50	0.007		0.007
			215.00	216.50	D009813	1.50	0.008		0.008
			216.50	218.00	D009814	1.50	0.008		0.008
			218.00	219.50	D009815	1.50	0.006		0.006
			219.50	221.00	D009816	1.50	0.005		0.005
			221.00	222.50	D009818	1.50	0.008		0.008
222.50	224.00	D009819	1.50	0.207		0.207			
224.00	225.60	D009820	1.60	0.265		0.265			
225.60	465.30	SY; FIN; MTY; POR <b>Syénite 55°; Grains fins; Grains moyens; Porphyrique</b> Syénite, grains fins à grains moyens et porphyrique.	225.60	227.00	D009821	1.40	0.194		0.194
			227.00	228.50	D009823	1.50	0.507		0.507
			228.50	230.00	D009824	1.50	0.163		0.163
			230.00	231.50	D009825	1.50	0.075		0.075
			231.50	233.00	D009826	1.50	0.092		0.092
			233.00	234.50	D009828	1.50	0.383		0.383
			234.50	236.00	D009829	1.50	0.267		0.267
			236.00	237.50	D009830	1.50	0.022		0.022
			237.50	239.00	D009831	1.50	0.023		0.023
			239.00	240.50	D009832	1.50	0.064		0.064
240.50	242.00	D009833	1.50	0.248		0.248			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	242.00	243.50	D009834	1.50	0.108		0.108
	243.50	245.00	D009835	1.50	0.037		0.037
	245.00	246.50	D009836	1.50	0.063		0.063
	246.50	248.00	D009838	1.50	0.088		0.088
	248.00	249.50	D009839	1.50	0.027		0.027
	249.50	251.00	D009840	1.50	0.009		0.009
	251.00	252.50	D009841	1.50	<0.005		0.001
	252.50	254.00	D009842	1.50	0.141		0.141
	254.00	255.50	D009843	1.50	0.044		0.044
	255.50	257.00	D009844	1.50	0.005		0.005
	257.00	258.50	D009845	1.50	0.005		0.005
	258.50	260.00	D009846	1.50	0.093		0.093
	260.00	261.50	D009848	1.50	0.010		0.010
	261.50	263.00	D009849	1.50	<0.005		0.001
	263.00	264.50	D009850	1.50	0.109		0.109
	264.50	266.00	D009851	1.50	0.133		0.133
	266.00	267.50	D009852	1.50	<0.005		0.001
	267.50	269.00	D009853	1.50	0.008		0.008
	269.00	270.50	D009854	1.50	0.024		0.024
	270.50	272.00	D009855	1.50	0.006		0.006
	272.00	273.50	D009856	1.50	<0.005		0.001
	273.50	275.00	D009858	1.50	<0.005		0.001
	275.00	276.50	D009859	1.50	1.110		1.110
	276.50	278.00	D009860	1.50	0.193		0.193
	278.00	279.50	D009861	1.50	<0.005		0.001
	279.50	281.00	D009863	1.50	0.005		0.005
	281.00	282.50	D009864	1.50	<0.005		0.001
	282.50	284.00	D009865	1.50	0.005		0.005
	284.00	285.50	D009866	1.50	<0.005		0.001
	285.50	287.00	D009868	1.50	<0.005		0.001
	287.00	288.50	D009869	1.50	0.006		0.006
	288.50	290.00	D009870	1.50	<0.005		0.001
	290.00	291.50	D009871	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	291.50	293.00	D009872	1.50	<0.005		0.001
	293.00	294.50	D009873	1.50	<0.005		0.001
	294.50	296.00	D009874	1.50	<0.005		0.001
	296.00	297.50	D009875	1.50	<0.005		0.001
	297.50	299.00	D009876	1.50	0.009		0.009
	299.00	300.50	D009878	1.50	<0.005		0.001
	300.50	302.00	D009879	1.50	<0.005		0.001
	302.00	303.50	D009880	1.50	<0.005		0.001
	303.50	305.00	D009881	1.50	<0.005		0.001
	305.00	306.50	D009882	1.50	0.014		0.014
	306.50	308.00	D009883	1.50	0.043		0.043
	308.00	309.50	D009884	1.50	0.006		0.006
	309.50	311.00	D009885	1.50	<0.005		0.001
	311.00	312.50	D009886	1.50	<0.005		0.001
	312.50	314.00	D009888	1.50	0.006		0.006
	314.00	315.50	D009889	1.50	<0.005		0.001
	315.50	317.00	D009890	1.50	<0.005		0.001
	317.00	318.50	D009891	1.50	<0.005		0.001
	318.50	320.00	D009892	1.50	<0.005		0.001
	320.00	321.50	D009893	1.50	<0.005		0.001
	321.50	323.00	D009894	1.50	<0.005		0.001
	323.00	324.50	D009895	1.50	<0.005		0.001
	324.50	326.00	D009896	1.50	<0.005		0.001
	326.00	327.50	D009898	1.50	<0.005		0.001
	327.50	329.00	D009899	1.50	<0.005		0.001
	329.00	330.50	D009900	1.50	<0.005		0.001
	330.50	332.00	D009901	1.50	<0.005		0.001
	332.00	333.50	D009903	1.50	0.006		0.006
	333.50	335.00	D009904	1.50	<0.005		0.001
	335.00	336.50	D009905	1.50	0.008		0.008
	336.50	338.00	D009906	1.50	<0.005		0.001
	338.00	339.50	D009908	1.50	<0.005		0.001
	339.50	341.00	D009909	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	341.00	342.50	D009910	1.50	0.009		0.009
	342.50	344.00	D009911	1.50	<0.005		0.001
	344.00	345.50	D009912	1.50	<0.005		0.001
	345.50	347.00	D009913	1.50	<0.005		0.001
	347.00	348.50	D009914	1.50	0.005		0.005
	348.50	350.00	D009915	1.50	0.008		0.008
	350.00	351.50	D009916	1.50	0.013		0.013
	351.50	353.00	D009918	1.50	0.114		0.114
	353.00	354.50	D009919	1.50	0.084		0.084
	354.50	356.00	D009920	1.50	0.015		0.015
	356.00	357.50	D009921	1.50	0.317		0.317
	357.50	359.00	D009922	1.50	<0.005		0.001
	359.00	360.50	D009923	1.50	0.377		0.377
	360.50	362.00	D009924	1.50	0.015		0.015
	362.00	363.50	D009925	1.50	0.038		0.038
	363.50	365.00	D009926	1.50	0.040		0.040
	365.00	366.50	D009928	1.50	<0.005		0.001
	366.50	368.00	D009929	1.50	0.010		0.010
	368.00	369.50	D009930	1.50	0.017		0.017
	369.50	371.00	D009931	1.50	0.010		0.010
	371.00	372.50	D009932	1.50	0.048		0.048
	372.50	374.00	D009933	1.50	0.022		0.022
	374.00	375.50	D009934	1.50	0.013		0.013
	375.50	377.00	D009935	1.50	<0.005		0.001
	377.00	378.50	D009936	1.50	0.054		0.054
	378.50	380.00	D009938	1.50	0.076		0.076
	380.00	381.50	D009939	1.50	0.010		0.010
	381.50	383.00	D009940	1.50	0.011		0.011
	383.00	384.50	D009941	1.50	<0.005		0.001
	384.50	386.00	D009943	1.50	<0.005		0.001
	386.00	387.50	D009944	1.50	<0.005		0.001
	387.50	389.00	D009945	1.50	<0.005		0.001
	389.00	390.50	D009946	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			390.50	392.00	D009948	1.50	<0.005		0.001
			392.00	393.50	D009949	1.50	<0.005		0.001
			393.50	395.00	D009950	1.50	0.006		0.006
			395.00	396.50	D009951	1.50	<0.005		0.001
			396.50	398.00	D009952	1.50	<0.005		0.001
			398.00	399.50	D009953	1.50	0.079		0.079
			399.50	401.00	D009954	1.50	<0.005		0.001
			401.00	402.50	D009955	1.50	<0.005		0.001
			402.50	404.00	D009956	1.50	0.177		0.177
			404.00	405.50	D009958	1.50	0.029		0.029
			405.50	407.00	D009959	1.50	<0.005		0.001
			407.00	408.50	D009960	1.50	0.031		0.031
			408.50	410.00	D009961	1.50	0.130		0.130
			410.00	411.50	D009962	1.50	0.274		0.274
			411.50	413.00	D009963	1.50	0.356		0.356
			413.00	414.50	D009964	1.50	<0.005		0.001
			414.50	416.00	D009965	1.50	<0.005		0.001
			416.00	417.50	D009966	1.50	0.036		0.036
			417.50	419.00	D009968	1.50	0.005		0.005
			419.00	420.50	D009969	1.50	0.027		0.027
			420.50	422.00	D009970	1.50	0.021		0.021
			422.00	423.50	D009971	1.50	1.330		1.330
423.50	425.00	SY; BRI	423.50	425.00	D009972	1.50	0.014		0.014
		<b>Syénite; Brèche intrusive</b>	425.00	426.50	D009973	1.50	0.017		0.017
		Syénite bréchifié avec de fragments anguleux à sub-anguleux.	426.50	428.00	D009974	1.50	0.025		0.025
			428.00	429.50	D009975	1.50	0.010		0.010
			429.50	431.00	D009976	1.50	0.021		0.021
			431.00	432.50	D009978	1.50	0.026		0.026
			432.50	434.00	D009979	1.50	0.018		0.018
			434.00	435.50	D009980	1.50	0.014		0.014
			435.50	437.00	D009981	1.50	0.008		0.008
			437.00	438.50	D009983	1.50	0.016		0.016
			438.50	440.00	D009984	1.50	0.621		0.621

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	440.00	441.50	D009985	1.50	0.343		0.343
	441.50	443.00	D009986	1.50	0.067		0.067
	443.00	444.50	D009988	1.50	0.064		0.064
	444.50	446.00	D009989	1.50	0.060		0.060
	446.00	447.50	D009990	1.50	0.380		0.380
	447.50	449.00	D009991	1.50	0.533		0.533
	449.00	450.50	D009992	1.50	0.007		0.007
	450.50	452.00	D009993	1.50	<0.005		0.001
	452.00	453.50	D009994	1.50	0.008		0.008
	453.50	455.00	D009995	1.50	0.024		0.024
	455.00	456.50	D009996	1.50	<0.005		0.001
	456.50	458.00	D009998	1.50	0.006		0.006
	458.00	459.50	D009999	1.50	0.462		0.462
	459.50	461.00	D010000	1.50	0.006		0.006
	461.00	462.50	D017001	1.50	<0.005		0.001
	462.50	464.00	D017003	1.50	<0.005		0.001
	464.00	465.30	D017004	1.30	<0.005		0.001
465.30	Fin du sondage Nombre d'échantillons : 312 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 462.70						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	16.00	D009657	D009656	1.50	<0.005	0.001
20.00	21.00	D009662	M1	1.00	<0.005	0.001
25.50	27.00	D009667	G2	1.50	3.920	3.920
39.00	40.50	D009677	D009676	1.50	0.006	0.006
52.00	53.00	D009687	C4	1.00	1.350	1.350
64.00	65.50	D009697	D009696	1.50	<0.005	0.001
70.00	71.50	D009702	M1	1.50	<0.005	0.001
76.00	77.50	D009707	D2	1.50	0.856	0.856
89.50	91.00	D009717	D009716	1.50	<0.005	0.001
103.00	104.50	D009727	M	1.50	3.000	3.000
116.50	118.00	D009737	D009736	1.50	0.005	0.005
122.50	124.00	D009742	M1	1.50	<0.005	0.001
128.50	130.00	D009747	G2	1.50	4.010	4.010
142.00	143.50	D009757	D009756	1.50	0.005	0.005
155.50	157.00	D009767	H	1.50	0.828	0.828
169.00	170.50	D009777	D009776	1.50	0.133	0.133
175.00	176.00	D009782	M1	1.00	<0.005	0.001
180.50	182.00	D009787	A3	1.50	0.590	0.590
194.00	195.50	D009797	D009796	1.50	0.021	0.021
206.00	207.50	D009807	B4	1.50	2.630	2.630
219.50	221.00	D009817	D009816	1.50	<0.005	0.001
225.60	227.00	D009822	M1	1.40	<0.005	0.001
231.50	233.00	D009827	C4	1.50	1.335	1.335
245.00	246.50	D009837	D009836	1.50	0.062	0.062
258.50	260.00	D009847	D2	1.50	0.809	0.809
272.00	273.50	D009857	D009856	1.50	0.005	0.005
278.00	279.50	D009862	M1	1.50	0.005	0.005
284.00	285.50	D009867	M	1.50	2.680	2.680
297.50	299.00	D009877	D009876	1.50	0.010	0.010
311.00	312.50	D009887	G2	1.50	4.020	4.020
324.50	326.00	D009897	D009896	1.50	<0.005	0.001
330.50	332.00	D009902	M1	1.50	<0.005	0.001
336.50	338.00	D009907	H	1.50	0.994	0.994

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
350.00	351.50	D009917	D009916	1.50	0.017	0.017
363.50	365.00	D009927	A3	1.50	0.591	0.591
377.00	378.50	D009937	D009936	1.50	0.069	0.069
383.00	384.50	D009942	M1	1.50	<0.005	0.001
389.00	390.50	D009947	G2	1.50	4.010	4.010
402.50	404.00	D009957	D009956	1.50	0.172	0.172
416.00	417.50	D009967	C4	1.50	1.325	1.325
429.50	431.00	D009977	D009976	1.50	0.048	0.048
435.50	437.00	D009982	M1	1.50	<0.005	0.001
441.50	443.00	D009987	D2	1.50	0.862	0.862
455.00	456.50	D009997	D009996	1.50	<0.005	0.001
461.00	462.50	D017002	M1	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-173**

Titre minier :

Section :                      630700

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-04-22

Date de description :

Au :                      2010-04-29

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      464.00 m

Est	630 700.4
Nord	5 374 300.8
Élévation	308.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	341.30°	-59.70°	Oui
Reflex	8.00	337.00°	-59.40°	Oui
Reflex	11.00	10.70°	-59.20°	Oui
Reflex	14.00	0.40°	-59.40°	Oui
Reflex	17.00	2.20°	-59.30°	Oui
Reflex	20.00	1.50°	-59.20°	Non
Reflex	23.00	1.20°	-59.10°	Non
Reflex	26.00	2.00°	-59.30°	Non
Reflex	29.00	0.80°	-59.00°	Non
Reflex	32.00	0.30°	-58.90°	Non
Reflex	35.00	0.80°	-58.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.00°	-58.90°	Non
Reflex	41.00	1.50°	-58.90°	Non
Reflex	44.00	0.20°	-58.80°	Non
Reflex	47.00	0.70°	-58.70°	Non
Reflex	50.00	358.70°	-58.50°	Non
Reflex	53.00	360.00°	-58.60°	Non
Reflex	56.00	358.80°	-58.50°	Non
Reflex	59.00	358.80°	-58.50°	Non
Reflex	62.00	359.30°	-58.60°	Non
Reflex	65.00	359.50°	-58.60°	Non
Reflex	68.00	359.80°	-58.60°	Non
Reflex	71.00	359.80°	-58.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.20°	-58.80°	Non	Reflex	173.00	1.50°	-58.10°	Non
Reflex	77.00	359.40°	-58.40°	Non	Reflex	176.00	1.70°	-58.10°	Non
Reflex	80.00	359.40°	-58.30°	Non	Reflex	179.00	1.30°	-58.00°	Non
Reflex	83.00	359.90°	-58.30°	Non	Reflex	182.00	4.30°	-57.90°	Oui
Reflex	86.00	359.60°	-58.30°	Non	Reflex	185.00	3.70°	-57.90°	Non
Reflex	89.00	359.80°	-58.20°	Non	Reflex	188.00	3.60°	-57.80°	Non
Reflex	92.00	359.80°	-58.30°	Non	Reflex	191.00	3.10°	-57.70°	Non
Reflex	95.00	359.80°	-58.30°	Non	Reflex	194.00	2.10°	-57.70°	Non
Reflex	98.00	359.60°	-58.30°	Non	Reflex	197.00	1.90°	-57.70°	Non
Reflex	101.00	359.50°	-58.30°	Non	Reflex	200.00	2.60°	-57.60°	Non
Reflex	104.00	359.40°	-58.30°	Non	Reflex	203.00	2.60°	-57.50°	Non
Reflex	107.00	359.30°	-58.30°	Non	Reflex	206.00	3.20°	-57.50°	Non
Reflex	110.00	359.90°	-58.30°	Non	Reflex	209.00	2.70°	-57.40°	Non
Reflex	113.00	2.20°	-58.30°	Oui	Reflex	212.00	2.50°	-57.30°	Non
Reflex	116.00	358.90°	-58.30°	Non	Reflex	215.00	3.10°	-57.30°	Non
Reflex	119.00	2.60°	-57.00°	Non	Reflex	218.00	3.10°	-57.10°	Non
Reflex	122.00	2.40°	-58.30°	Non	Reflex	221.00	2.40°	-57.00°	Non
Reflex	125.00	1.20°	-58.30°	Oui	Reflex	224.00	1.60°	-57.00°	Non
Reflex	128.00	3.00°	-58.40°	Non	Reflex	227.00	1.60°	-56.90°	Non
Reflex	131.00	1.50°	-58.30°	Non	Reflex	230.00	2.20°	-56.90°	Non
Reflex	134.00	0.80°	-58.30°	Non	Reflex	233.00	0.90°	-56.80°	Non
Reflex	137.00	1.70°	-58.30°	Non	Reflex	236.00	0.90°	-56.80°	Non
Reflex	140.00	2.70°	-58.30°	Non	Reflex	239.00	0.40°	-56.80°	Non
Reflex	143.00	2.20°	-58.30°	Non	Reflex	242.00	1.10°	-56.80°	Non
Reflex	146.00	2.00°	-58.30°	Non	Reflex	245.00	0.30°	-56.80°	Non
Reflex	149.00	0.10°	-58.30°	Non	Reflex	248.00	0.30°	-56.80°	Non
Reflex	152.00	0.60°	-58.30°	Non	Reflex	251.00	0.10°	-56.80°	Non
Reflex	155.00	359.70°	-58.30°	Non	Reflex	254.00	358.80°	-56.80°	Non
Reflex	158.00	1.60°	-58.30°	Non	Reflex	257.00	1.10°	-56.80°	Non
Reflex	161.00	3.10°	-58.40°	Non	Reflex	260.00	1.60°	-56.80°	Non
Reflex	164.00	3.00°	-58.20°	Non	Reflex	263.00	1.60°	-56.70°	Non
Reflex	167.00	2.20°	-58.10°	Non	Reflex	266.00	3.10°	-56.70°	Non
Reflex	170.00	4.70°	-58.20°	Oui	Reflex	269.00	3.40°	-56.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	1.90°	-56.70°	Non	Reflex	371.00	3.10°	-56.50°	Non
Reflex	275.00	1.80°	-56.80°	Non	Reflex	374.00	3.40°	-56.60°	Non
Reflex	278.00	1.90°	-56.70°	Non	Reflex	377.00	2.00°	-56.50°	Non
Reflex	281.00	0.20°	-56.70°	Non	Reflex	380.00	3.70°	-56.50°	Non
Reflex	284.00	0.20°	-56.70°	Non	Reflex	383.00	3.50°	-56.60°	Non
Reflex	287.00	0.60°	-56.70°	Non	Reflex	386.00	4.10°	-56.60°	Non
Reflex	290.00	0.20°	-56.70°	Non	Reflex	389.00	3.80°	-56.60°	Non
Reflex	293.00	359.90°	-56.70°	Non	Reflex	392.00	3.90°	-56.60°	Non
Reflex	296.00	0.10°	-56.70°	Non	Reflex	395.00	3.60°	-56.70°	Non
Reflex	299.00	1.60°	-56.70°	Non	Reflex	398.00	4.00°	-56.70°	Non
Reflex	302.00	1.40°	-56.60°	Non	Reflex	401.00	5.50°	-56.80°	Oui
Reflex	305.00	1.30°	-56.60°	Non	Reflex	404.00	4.60°	-56.80°	Non
Reflex	308.00	1.60°	-56.70°	Non	Reflex	407.00	5.70°	-56.80°	Oui
Reflex	311.00	0.70°	-56.60°	Non	Reflex	410.00	4.00°	-56.80°	Non
Reflex	314.00	2.50°	-56.60°	Non	Reflex	413.00	3.20°	-56.80°	Non
Reflex	317.00	2.20°	-56.60°	Non	Reflex	416.00	3.40°	-56.80°	Non
Reflex	320.00	1.30°	-56.60°	Non	Reflex	419.00	4.60°	-56.80°	Non
Reflex	323.00	359.20°	-56.50°	Non	Reflex	422.00	3.80°	-56.90°	Non
Reflex	326.00	1.10°	-56.60°	Non	Reflex	425.00	4.70°	-56.80°	Non
Reflex	329.00	359.70°	-56.50°	Non	Reflex	428.00	6.70°	-56.90°	Non
Reflex	332.00	1.40°	-56.50°	Non	Reflex	431.00	6.40°	-56.90°	Non
Reflex	335.00	3.70°	-56.50°	Oui	Reflex	434.00	6.20°	-56.90°	Non
Reflex	338.00	0.30°	-56.50°	Non	Reflex	437.00	6.10°	-57.00°	Non
Reflex	341.00	3.30°	-56.50°	Non	Reflex	440.00	6.70°	-56.90°	Non
Reflex	344.00	3.50°	-56.50°	Oui	Reflex	443.00	5.90°	-57.00°	Non
Reflex	347.00	1.50°	-56.50°	Non	Reflex	446.00	5.90°	-57.00°	Non
Reflex	350.00	0.70°	-56.50°	Non	Reflex	449.00	6.20°	-57.00°	Non
Reflex	353.00	2.20°	-56.50°	Non	Reflex	452.00	6.30°	-57.10°	Non
Reflex	356.00	2.00°	-56.60°	Non	Reflex	455.00	6.70°	-57.10°	Non
Reflex	359.00	1.50°	-56.60°	Non	Reflex	458.00	6.40°	-57.00°	Non
Reflex	362.00	4.50°	-56.60°	Non	Reflex	461.00	6.30°	-57.00°	Non
Reflex	365.00	5.00°	-56.50°	Non	Reflex	464.00	6.90°	-57.00°	Non
Reflex	368.00	4.10°	-56.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	7.00	MT						
		<b>Mort-terrain</b>						
7.00	13.90	BA; FIN; AMY	7.00	8.50	D017380	1.50	<0.005	0.001
		<b>Basalte; Grains fins; Amygdalaire</b>	8.50	10.00	D017381	1.50	<0.005	0.001
		Basalte à grains fins et à passage amygdalaire.	10.00	11.50	D017382	1.50	<0.005	0.001
			11.50	13.00	D017383	1.50	<0.005	0.001
			13.00	13.90	D017384	0.90	<0.005	0.001
13.90	464.00	SY; FIN; POR	13.90	15.50	D017385	1.60	<0.005	0.001
		<b>Syénite 65°; Grains fins; Porphyrique</b>	15.50	17.00	D017386	1.50	0.013	0.013
		Syénite à grains fins avec passage porphyrique.	17.00	18.50	D017388	1.50	0.117	0.117
			18.50	20.00	D017389	1.50	0.076	0.076
			20.00	21.50	D017390	1.50	0.060	0.060
			21.50	23.00	D017391	1.50	0.276	0.276
			23.00	24.50	D017392	1.50	0.188	0.188
			24.50	26.00	D017393	1.50	0.347	0.347
			26.00	27.50	D017394	1.50	0.011	0.011
			27.50	29.00	D017395	1.50	<0.005	0.001
			29.00	30.50	D017396	1.50	0.037	0.037
			30.50	32.00	D017398	1.50	<0.005	0.001
			32.00	33.50	D017399	1.50	<0.005	0.001
			33.50	35.00	D017400	1.50	<0.005	0.001
			35.00	36.50	D017401	1.50	<0.005	0.001
			36.50	38.00	D017403	1.50	<0.005	0.001
			38.00	39.50	D017404	1.50	0.016	0.016
			39.50	41.00	D017405	1.50	<0.005	0.001
			41.00	42.50	D017406	1.50	<0.005	0.001
			42.50	44.00	D017408	1.50	<0.005	0.001
			44.00	45.50	D017409	1.50	0.005	0.005
			45.50	47.00	D017410	1.50	<0.005	0.001
			47.00	48.50	D017411	1.50	<0.005	0.001
			48.50	50.00	D017412	1.50	0.007	0.007
			50.00	51.50	D017413	1.50	<0.005	0.001
			51.50	53.00	D017414	1.50	0.010	0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	53.00	54.50	D017415	1.50	0.376		0.376
	54.50	56.00	D017416	1.50	0.005		0.005
	56.00	57.50	D017418	1.50	0.047		0.047
	57.50	59.00	D017419	1.50	0.437		0.437
	59.00	60.50	D017420	1.50	0.056		0.056
	60.50	62.00	D017421	1.50	0.006		0.006
	62.00	63.50	D017422	1.50	<0.005		0.001
	63.50	65.00	D017423	1.50	0.013		0.013
	65.00	66.50	D017424	1.50	0.079		0.079
	66.50	68.00	D017425	1.50	0.019		0.019
	68.00	69.50	D017426	1.50	0.239		0.239
	69.50	71.00	D017428	1.50	0.101		0.101
	71.00	72.50	D017429	1.50	0.021		0.021
	72.50	74.00	D017430	1.50	1.175		1.175
	74.00	75.50	D017431	1.50	0.115		0.115
	75.50	77.00	D017432	1.50	0.070		0.070
	77.00	78.50	D017433	1.50	0.277		0.277
	78.50	80.00	D017434	1.50	2.150		2.150
	80.00	81.50	D017435	1.50	0.222		0.222
	81.50	83.00	D017436	1.50	0.082		0.082
	83.00	84.50	D017438	1.50	0.084		0.084
	84.50	86.00	D017439	1.50	0.050		0.050
	86.00	87.50	D017440	1.50	<0.005		0.001
	87.50	89.00	D017441	1.50	<0.005		0.001
	89.00	90.50	D017443	1.50	0.026		0.026
	90.50	92.00	D017444	1.50	0.018		0.018
	92.00	93.50	D017445	1.50	0.008		0.008
	93.50	95.00	D017446	1.50	0.025		0.025
	95.00	96.50	D017448	1.50	>10.0	18.40	18.400
	96.50	98.00	D017449	1.50	0.114		0.114
	98.00	99.50	D017450	1.50	0.120		0.120
	99.50	101.00	D017451	1.50	0.245		0.245
	101.00	102.50	D017452	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	102.50	104.00	D017453	1.50	0.012		0.012
	104.00	105.50	D017454	1.50	0.005		0.005
	105.50	107.00	D017455	1.50	<0.005		0.001
	107.00	108.50	D017456	1.50	0.009		0.009
	108.50	110.00	D017458	1.50	0.013		0.013
	110.00	111.50	D017459	1.50	0.007		0.007
	111.50	113.00	D017460	1.50	<0.005		0.001
	113.00	114.50	D017461	1.50	0.018		0.018
	114.50	116.00	D017462	1.50	0.027		0.027
	116.00	117.50	D017463	1.50	<0.005		0.001
	117.50	119.00	D017464	1.50	0.005		0.005
	119.00	120.50	D017465	1.50	<0.005		0.001
	120.50	122.00	D017466	1.50	0.005		0.005
	122.00	123.50	D017468	1.50	<0.005		0.001
	123.50	125.00	D017469	1.50	<0.005		0.001
	125.00	126.50	D017470	1.50	<0.005		0.001
	126.50	128.00	D017471	1.50	0.019		0.019
	128.00	129.50	D017472	1.50	0.157		0.157
	129.50	131.00	D017473	1.50	0.033		0.033
	131.00	132.50	D017474	1.50	<0.005		0.001
	132.50	134.00	D017475	1.50	0.006		0.006
	134.00	135.50	D017476	1.50	0.013		0.013
	135.50	137.00	D017478	1.50	<0.005		0.001
	137.00	138.50	D017479	1.50	0.006		0.006
	138.50	140.00	D017480	1.50	0.263		0.263
	140.00	141.50	D017481	1.50	<0.005		0.001
	141.50	143.00	D017483	1.50	0.008		0.008
	143.00	144.50	D017484	1.50	0.081		0.081
	144.50	146.00	D017485	1.50	<0.005		0.001
	146.00	147.50	D017486	1.50	0.087		0.087
	147.50	149.00	D017488	1.50	0.016		0.016
	149.00	150.50	D017489	1.50	1.200		1.200
	150.50	152.00	D017490	1.50	1.100		1.100



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	152.00	153.50	D017491	1.50	0.155		0.155
	153.50	155.00	D017492	1.50	<0.005		0.001
	155.00	156.50	D017493	1.50	0.251		0.251
	156.50	158.00	D017494	1.50	0.020		0.020
	158.00	159.50	D017495	1.50	0.090		0.090
	159.50	161.00	D017496	1.50	0.316		0.316
	161.00	162.50	D017498	1.50	0.892		0.892
	162.50	164.00	D017499	1.50	0.490		0.490
	164.00	165.50	D017500	1.50	0.869		0.869
	165.50	167.00	D017501	1.50	0.124		0.124
	167.00	168.50	D017502	1.50	0.151		0.151
	168.50	170.00	D017503	1.50	0.103		0.103
	170.00	171.50	D017504	1.50	0.993		0.993
	171.50	173.00	D017505	1.50	1.265		1.265
	173.00	174.50	D017506	1.50	0.012		0.012
	174.50	176.00	D017508	1.50	0.006		0.006
	176.00	177.50	D017509	1.50	0.008		0.008
	177.50	179.00	D017510	1.50	0.005		0.005
	179.00	180.50	D017511	1.50	0.008		0.008
	180.50	182.00	D017512	1.50	<0.005		0.001
	182.00	183.50	D017513	1.50	0.005		0.005
	183.50	185.00	D017514	1.50	<0.005		0.001
	185.00	186.50	D017515	1.50	0.005		0.005
	186.50	188.00	D017516	1.50	0.005		0.005
	188.00	189.50	D017518	1.50	<0.005		0.001
	189.50	191.00	D017519	1.50	<0.005		0.001
	191.00	192.50	D017520	1.50	0.012		0.012
	192.50	194.00	D017521	1.50	0.005		0.005
	194.00	195.50	D017523	1.50	<0.005		0.001
	195.50	197.00	D017524	1.50	0.005		0.005
	197.00	198.50	D017525	1.50	1.265		1.265
	198.50	200.00	D017526	1.50	0.018		0.018
	200.00	201.50	D017528	1.50	0.028		0.028

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	201.50	203.00	D017529	1.50	<0.005		0.001
	203.00	204.50	D017530	1.50	0.017		0.017
	204.50	206.00	D017531	1.50	<0.005		0.001
	206.00	207.50	D017532	1.50	0.007		0.007
	207.50	209.00	D017533	1.50	0.006		0.006
	209.00	210.50	D017534	1.50	0.016		0.016
	210.50	212.00	D017535	1.50	0.005		0.005
	212.00	213.50	D017536	1.50	0.006		0.006
	213.50	215.00	D017538	1.50	0.008		0.008
	215.00	216.50	D017539	1.50	0.006		0.006
	216.50	218.00	D017540	1.50	0.005		0.005
	218.00	219.50	D017541	1.50	0.012		0.012
	219.50	221.00	D017542	1.50	0.015		0.015
	221.00	222.50	D017543	1.50	0.009		0.009
	222.50	224.00	D017544	1.50	<0.005		0.001
	224.00	225.50	D017545	1.50	0.543		0.543
	225.50	227.00	D017546	1.50	0.339		0.339
	227.00	228.50	D017548	1.50	0.884		0.884
	228.50	230.00	D017549	1.50	0.010		0.010
	230.00	231.50	D017550	1.50	0.131		0.131
	231.50	233.00	D017551	1.50	0.123		0.123
	233.00	234.50	D017552	1.50	0.098		0.098
	234.50	236.00	D017553	1.50	0.021		0.021
	236.00	237.50	D017554	1.50	0.020		0.020
	237.50	239.00	D017555	1.50	0.067		0.067
	239.00	240.50	D017556	1.50	0.070		0.070
	240.50	242.00	D017558	1.50	0.080		0.080
	242.00	243.50	D017559	1.50	0.201		0.201
	243.50	245.00	D017560	1.50	0.041		0.041
	245.00	246.50	D017561	1.50	0.009		0.009
	246.50	248.00	D017563	1.50	0.035		0.035
	248.00	249.50	D017564	1.50	0.041		0.041
	249.50	251.00	D017565	1.50	0.047		0.047

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	251.00	252.50	D017566	1.50	0.207		0.207
	252.50	254.00	D017568	1.50	0.033		0.033
	254.00	255.50	D017569	1.50	<0.005		0.001
	255.50	257.00	D017570	1.50	0.007		0.007
	257.00	258.50	D017571	1.50	<0.005		0.001
	258.50	260.00	D017572	1.50	<0.005		0.001
	260.00	261.50	D017573	1.50	0.007		0.007
	261.50	263.00	D017574	1.50	0.011		0.011
	263.00	264.50	D017575	1.50	1.045		1.045
	264.50	266.00	D017576	1.50	0.276		0.276
	266.00	267.50	D017578	1.50	0.006		0.006
	267.50	269.00	D017579	1.50	0.516		0.516
	269.00	270.50	D017580	1.50	0.014		0.014
	270.50	272.00	D017581	1.50	<0.005		0.001
	272.00	273.50	D017582	1.50	0.006		0.006
	273.50	275.00	D017583	1.50	0.007		0.007
	275.00	276.50	D017584	1.50	<0.005		0.001
	276.50	278.00	D017585	1.50	0.092		0.092
	278.00	279.50	D017586	1.50	0.020		0.020
	279.50	281.00	D017588	1.50	0.017		0.017
	281.00	282.50	D017589	1.50	2.610		2.610
	282.50	284.00	D017590	1.50	0.036		0.036
	284.00	285.50	D017591	1.50	<0.005		0.001
	285.50	287.00	D017592	1.50	0.027		0.027
	287.00	288.50	D017593	1.50	0.007		0.007
	288.50	290.00	D017594	1.50	<0.005		0.001
	290.00	291.50	D017595	1.50	0.048		0.048
	291.50	293.00	D017596	1.50	0.217		0.217
	293.00	294.50	D017598	1.50	0.017		0.017
	294.50	296.00	D017599	1.50	0.199		0.199
	296.00	297.50	D017600	1.50	0.030		0.030
	297.50	299.00	D017601	1.50	0.101		0.101
	299.00	300.50	D017603	1.50	0.048		0.048

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	300.50	302.00	D017604	1.50	0.203		0.203
	302.00	303.50	D017605	1.50	0.026		0.026
	303.50	305.00	D017606	1.50	<0.005		0.001
	305.00	306.50	D017608	1.50	0.016		0.016
	306.50	308.00	D017609	1.50	0.042		0.042
	308.00	309.50	D017610	1.50	0.027		0.027
	309.50	311.00	D017611	1.50	0.358		0.358
	311.00	312.50	D017612	1.50	0.751		0.751
	312.50	314.00	D017613	1.50	0.005		0.005
	314.00	315.50	D017614	1.50	0.748		0.748
	315.50	317.00	D017615	1.50	0.239		0.239
	317.00	318.50	D017616	1.50	0.055		0.055
	318.50	320.00	D017618	1.50	0.050		0.050
	320.00	321.50	D017619	1.50	<0.005		0.001
	321.50	323.00	D017620	1.50	0.417		0.417
	323.00	324.50	D017621	1.50	0.026		0.026
	324.50	326.00	D017622	1.50	0.018		0.018
	326.00	327.50	D017623	1.50	0.034		0.034
	327.50	329.00	D017624	1.50	0.034		0.034
	329.00	330.50	D017625	1.50	<0.005		0.001
	330.50	332.00	D017626	1.50	0.011		0.011
	332.00	333.50	D017628	1.50	1.040		1.040
	333.50	335.00	D017629	1.50	0.201		0.201
	335.00	336.50	D017630	1.50	0.141		0.141
	336.50	338.00	D017631	1.50	0.046		0.046
	338.00	339.50	D017632	1.50	0.008		0.008
	339.50	341.00	D017633	1.50	<0.005		0.001
	341.00	342.50	D017634	1.50	<0.005		0.001
	342.50	344.00	D017635	1.50	<0.005		0.001
	344.00	345.50	D017636	1.50	0.047		0.047
	345.50	347.00	D017638	1.50	0.021		0.021
	347.00	348.00	D017639	1.00	0.006		0.006
	348.00	349.00	D017640	1.00	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	349.00	350.00	D017641	1.00	0.059		0.059
	350.00	351.50	D017643	1.50	<0.005		0.001
	351.50	353.00	D017644	1.50	0.025		0.025
	353.00	354.50	D017645	1.50	<0.005		0.001
	354.50	356.00	D017646	1.50	0.032		0.032
	356.00	357.50	D017648	1.50	0.040		0.040
	357.50	359.00	D017649	1.50	0.470		0.470
	359.00	360.50	D017650	1.50	<0.005		0.001
	360.50	362.00	D017651	1.50	0.489		0.489
	362.00	363.50	D017652	1.50	0.251		0.251
	363.50	365.00	D017653	1.50	0.165		0.165
	365.00	366.50	D017654	1.50	<0.005		0.001
	366.50	368.00	D017655	1.50	<0.005		0.001
	368.00	369.50	D017656	1.50	<0.005		0.001
	369.50	371.00	D017658	1.50	<0.005		0.001
	371.00	372.50	D017659	1.50	<0.005		0.001
	372.50	374.00	D017660	1.50	<0.005		0.001
	374.00	375.50	D017661	1.50	<0.005		0.001
	375.50	377.00	D017662	1.50	<0.005		0.001
	377.00	378.50	D017663	1.50	<0.005		0.001
	378.50	380.00	D017664	1.50	<0.005		0.001
	380.00	381.50	D017665	1.50	<0.005		0.001
	381.50	383.00	D017666	1.50	0.119		0.119
	383.00	384.50	D017668	1.50	0.063		0.063
	384.50	386.00	D017669	1.50	<0.005		0.001
	386.00	387.50	D017670	1.50	0.008		0.008
	387.50	389.00	D017671	1.50	0.049		0.049
	389.00	390.50	D017672	1.50	0.009		0.009
	390.50	392.00	D017673	1.50	<0.005		0.001
	392.00	393.50	D017674	1.50	0.039		0.039
	393.50	395.00	D017675	1.50	0.010		0.010
	395.00	396.50	D017676	1.50	<0.005		0.001
	396.50	398.00	D017678	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	398.00	399.50	D017679	1.50	0.060		0.060
	399.50	401.00	D017680	1.50	<0.005		0.001
	401.00	402.50	D017681	1.50	<0.005		0.001
	402.50	404.00	D017683	1.50	<0.005		0.001
	404.00	405.50	D017684	1.50	<0.005		0.001
	405.50	407.00	D017685	1.50	0.034		0.034
	407.00	408.50	D017686	1.50	<0.005		0.001
	408.50	410.00	D017688	1.50	0.006		0.006
	410.00	411.50	D017689	1.50	0.009		0.009
	411.50	413.00	D017690	1.50	0.005		0.005
	413.00	414.50	D017691	1.50	<0.005		0.001
	414.50	416.00	D017692	1.50	<0.005		0.001
	416.00	417.50	D017693	1.50	0.005		0.005
	417.50	419.00	D017694	1.50	<0.005		0.001
	419.00	420.50	D017695	1.50	<0.005		0.001
	420.50	422.00	D017696	1.50	<0.005		0.001
	422.00	423.50	D017698	1.50	<0.005		0.001
	423.50	425.00	D017699	1.50	1.435		1.435
	425.00	426.50	D017700	1.50	<0.005		0.001
	426.50	428.00	D017701	1.50	<0.005		0.001
	428.00	429.50	D017702	1.50	0.006		0.006
	429.50	431.00	D017703	1.50	<0.005		0.001
	431.00	432.50	D017704	1.50	<0.005		0.001
	432.50	434.00	D017705	1.50	0.005		0.005
	434.00	435.50	D017706	1.50	0.011		0.011
	435.50	437.00	D017708	1.50	0.006		0.006
	437.00	438.50	D017709	1.50	0.006		0.006
	438.50	440.00	D017710	1.50	<0.005		0.001
	440.00	441.50	D017711	1.50	<0.005		0.001
	441.50	443.00	D017712	1.50	<0.005		0.001
	443.00	444.50	D017713	1.50	<0.005		0.001
	444.50	446.00	D017714	1.50	<0.005		0.001
	446.00	447.50	D017715	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	447.50	449.00	D017716	1.50	0.007		0.007
	449.00	450.50	D017718	1.50	<0.005		0.001
	450.50	452.00	D017719	1.50	<0.005		0.001
	452.00	453.50	D017720	1.50	0.023		0.023
	453.50	455.00	D017721	1.50	0.008		0.008
	455.00	456.50	D017723	1.50	<0.005		0.001
	456.50	458.00	D017724	1.50	0.009		0.009
	458.00	459.00	D017725	1.00	<0.005		0.001
	459.00	460.50	D017726	1.50	<0.005		0.001
	460.50	462.00	D017728	1.50	<0.005		0.001
	462.00	463.00	D017729	1.00	<0.005		0.001
	463.00	464.00	D017730	1.00	<0.005		0.001
464.00	Fin du sondage Nombre d'échantillons : 307 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 457.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.50	17.00	D017387	G2	1.50	4.110	4.110
29.00	30.50	D017397	D017396	1.50	0.019	0.019
35.00	36.50	D017402	M1	1.50	<0.005	0.001
41.00	42.50	D017407	J	1.50	0.804	0.804
54.50	56.00	D017417	D017416	1.50	<0.005	0.001
68.00	69.50	D017427	K	1.50	0.992	0.992
81.50	83.00	D017437	D017436	1.50	0.080	0.080
87.50	89.00	D017442	M1	1.50	<0.005	0.001
93.50	95.00	D017447	L	1.50	2.150	2.150
107.00	108.50	D017457	D017456	1.50	0.009	0.009
120.50	122.00	D017467	M	1.50	3.240	3.240
134.00	135.50	D017477	D017476	1.50	<0.005	0.001
140.00	141.50	D017482	M1	1.50	<0.005	0.001
146.00	147.50	D017487	J	1.50	0.779	0.779
159.50	161.00	D017497	D017496	1.50	0.315	0.315
173.00	174.50	D017507	K	1.50	1.065	1.065
186.50	188.00	D017517	D017516	1.50	0.007	0.007
192.50	194.00	D017522	M1	1.50	<0.005	0.001
198.50	200.00	D017527	L	1.50	2.290	2.290
212.00	213.50	D017537	D017536	1.50	0.005	0.005
225.50	227.00	D017547	M	1.50	3.040	3.040
239.00	240.50	D017557	D017556	1.50	0.088	0.088
245.00	246.50	D017562	M1	1.50	<0.005	0.001
251.00	252.50	D017567	J	1.50	0.763	0.763
264.50	266.00	D017577	D017576	1.50	0.259	0.259
278.00	279.50	D017587	K	1.50	0.996	0.996
291.50	293.00	D017597	D017596	1.50	0.219	0.219
297.50	299.00	D017602	M1	1.50	<0.005	0.001
303.50	305.00	D017607	L	1.50	2.140	2.140
317.00	318.50	D017617	D017616	1.50	0.057	0.057
330.50	332.00	D017627	M	1.50		
344.00	345.50	D017637	D017636	1.50	0.045	0.045
349.00	350.00	D017642	M1	1.00	<0.005	0.001



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
354.50	356.00	D017647	J	1.50	0.742	0.742
368.00	369.50	D017657	D017656	1.50	<0.005	0.001
381.50	383.00	D017667	K	1.50	0.988	0.988
395.00	396.50	D017677	D017676	1.50	<0.005	0.001
401.00	402.50	D017682	M1	1.50	<0.005	0.001
407.00	408.50	D017687	L	1.50	2.450	2.450
420.50	422.00	D017697	D017696	1.50	<0.005	0.001
434.00	435.50	D017707	M	1.50	3.290	3.290
447.50	449.00	D017717	D017716	1.50	<0.005	0.001
453.50	455.00	D017722	M1	1.50	<0.005	0.001
459.00	460.50	D017727	J	1.50	0.799	0.799

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-174**

Titre minier :

Section :                      631000

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Guy Gbaguidi

Lot :

Du :                              2010-05-09

Date de description :

Au :                              2010-05-14

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      447.21 m

Est	631 000.1
Nord	5 374 350.9
Élévation	312.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	0.00°	0.00°	Non
Reflex	3.00	359.70°	-59.20°	Non
Reflex	6.00	0.20°	-59.30°	Non
Reflex	9.00	0.50°	-59.20°	Non
Reflex	12.00	0.40°	-59.20°	Non
Reflex	15.00	0.30°	-59.20°	Non
Reflex	18.00	0.10°	-59.20°	Non
Reflex	21.00	360.00°	-59.20°	Non
Reflex	24.00	0.10°	-59.00°	Non
Reflex	27.00	0.10°	-59.00°	Non
Reflex	30.00	0.10°	-58.90°	Non
Reflex	33.00	0.30°	-59.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	0.30°	-59.00°	Non
Reflex	39.00	0.30°	-58.90°	Non
Reflex	42.00	0.40°	-59.00°	Non
Reflex	45.00	0.40°	-59.00°	Non
Reflex	48.00	0.70°	-59.00°	Non
Reflex	51.00	0.60°	-58.90°	Non
Reflex	54.00	1.00°	-58.90°	Non
Reflex	57.00	1.00°	-58.90°	Non
Reflex	60.00	0.90°	-58.90°	Non
Reflex	63.00	1.10°	-58.90°	Non
Reflex	66.00	1.20°	-58.90°	Non
Reflex	69.00	1.40°	-58.90°	Non

Description

Open à 447.2 m.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	72.00	1.30°	-58.90°	Non
Reflex	75.00	1.20°	-58.90°	Non
Reflex	78.00	1.30°	-58.80°	Non
Reflex	81.00	1.30°	-58.80°	Non
Reflex	84.00	1.50°	-58.70°	Non
Reflex	87.00	1.40°	-58.80°	Non
Reflex	90.00	1.50°	-58.80°	Non
Reflex	93.00	1.40°	-58.80°	Non
Reflex	96.00	1.40°	-58.70°	Non
Reflex	99.00	1.50°	-58.70°	Non
Reflex	102.00	1.30°	-58.70°	Non
Reflex	105.00	1.30°	-58.60°	Non
Reflex	108.00	1.40°	-58.70°	Non
Reflex	111.00	1.90°	-58.70°	Non
Reflex	114.00	1.60°	-58.70°	Non
Reflex	117.00	2.60°	-58.70°	Non
Reflex	120.00	2.80°	-58.70°	Non
Reflex	123.00	1.70°	-58.80°	Non
Reflex	126.00	1.70°	-58.70°	Non
Reflex	129.00	2.80°	-58.70°	Non
Reflex	132.00	3.50°	-58.60°	Non
Reflex	135.00	3.10°	-58.60°	Non
Reflex	138.00	3.70°	-58.50°	Non
Reflex	141.00	4.10°	-58.50°	Non
Reflex	144.00	3.40°	-58.40°	Oui
Reflex	147.00	4.10°	-58.50°	Non
Reflex	150.00	3.90°	-58.40°	Non
Reflex	153.00	2.90°	-58.40°	Non
Reflex	156.00	3.30°	-58.50°	Non
Reflex	159.00	4.50°	-58.40°	Non
Reflex	162.00	2.10°	-58.50°	Non
Reflex	165.00	14.40°	-58.50°	Oui
Reflex	168.00	1.80°	-58.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	171.00	3.20°	-58.50°	Non
Reflex	174.00	15.80°	-58.50°	Oui
Reflex	177.00	3.90°	-58.50°	Non
Reflex	180.00	3.80°	-58.50°	Non
Reflex	183.00	4.90°	-58.50°	Non
Reflex	186.00	3.90°	-58.50°	Non
Reflex	189.00	4.20°	-58.50°	Non
Reflex	192.00	3.80°	-58.50°	Non
Reflex	195.00	4.90°	-58.50°	Non
Reflex	198.00	4.00°	-58.50°	Non
Reflex	201.00	5.30°	-58.50°	Non
Reflex	204.00	5.70°	-58.50°	Non
Reflex	207.00	6.00°	-58.50°	Non
Reflex	210.00	4.70°	-58.50°	Non
Reflex	213.00	5.80°	-58.60°	Non
Reflex	216.00	4.80°	-58.60°	Non
Reflex	219.00	4.80°	-58.50°	Non
Reflex	222.00	28.70°	-58.40°	Oui
Reflex	225.00	5.90°	-58.50°	Non
Reflex	228.00	6.90°	-58.50°	Non
Reflex	231.00	6.90°	-58.50°	Non
Reflex	234.00	4.80°	-58.50°	Oui
Reflex	237.00	5.70°	-58.50°	Non
Reflex	240.00	6.60°	-58.50°	Non
Reflex	243.00	6.80°	-58.50°	Non
Reflex	246.00	6.30°	-58.50°	Non
Reflex	249.00	5.90°	-58.40°	Non
Reflex	252.00	5.70°	-58.40°	Non
Reflex	255.00	5.50°	-58.30°	Non
Reflex	258.00	5.20°	-58.20°	Non
Reflex	261.00	5.60°	-58.20°	Non
Reflex	264.00	5.30°	-58.20°	Non
Reflex	267.00	5.50°	-58.20°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	270.00	5.70°	-58.20°	Non	Reflex	369.00	9.40°	-57.90°	Non
Reflex	273.00	6.20°	-58.10°	Non	Reflex	372.00	11.00°	-57.90°	Non
Reflex	276.00	6.20°	-58.10°	Non	Reflex	375.00	10.20°	-57.90°	Non
Reflex	279.00	5.00°	-58.00°	Non	Reflex	378.00	10.60°	-57.90°	Non
Reflex	282.00	5.90°	-58.00°	Non	Reflex	381.00	10.70°	-57.90°	Non
Reflex	285.00	5.80°	-58.00°	Non	Reflex	384.00	31.00°	-57.90°	Oui
Reflex	288.00	6.30°	-58.00°	Non	Reflex	387.00	10.40°	-58.00°	Non
Reflex	291.00	7.20°	-58.00°	Non	Reflex	390.00	31.20°	-57.90°	Oui
Reflex	294.00	7.40°	-58.00°	Non	Reflex	393.00	10.20°	-57.90°	Non
Reflex	297.00	8.00°	-58.00°	Non	Reflex	396.00	11.10°	-57.90°	Non
Reflex	300.00	6.10°	-58.00°	Non	Reflex	399.00	29.10°	-57.90°	Oui
Reflex	303.00	22.20°	-58.00°	Oui	Reflex	402.00	11.20°	-57.90°	Non
Reflex	306.00	5.20°	-58.00°	Non	Reflex	405.00	10.40°	-58.00°	Oui
Reflex	309.00	5.90°	-58.00°	Non	Reflex	408.00	12.10°	-58.00°	Non
Reflex	312.00	4.40°	-58.00°	Non	Reflex	411.00	12.20°	-57.90°	Non
Reflex	315.00	4.40°	-58.00°	Non	Reflex	414.00	11.80°	-57.90°	Non
Reflex	318.00	3.70°	-57.90°	Oui	Reflex	417.00	11.50°	-57.90°	Non
Reflex	321.00	6.70°	-57.90°	Non	Reflex	420.00	9.10°	-57.90°	Non
Reflex	324.00	8.70°	-57.90°	Non	Reflex	423.00	9.60°	-57.80°	Non
Reflex	327.00	9.20°	-57.80°	Non	Reflex	426.00	8.80°	-57.80°	Non
Reflex	330.00	8.70°	-57.90°	Non	Reflex	429.00	8.60°	-57.80°	Non
Reflex	333.00	9.40°	-57.90°	Non	Reflex	432.00	8.90°	-57.90°	Non
Reflex	336.00	9.20°	-57.90°	Non	Reflex	435.00	9.20°	-57.80°	Non
Reflex	339.00	9.20°	-57.90°	Non	Reflex	438.00	9.30°	-57.70°	Non
Reflex	342.00	8.20°	-57.90°	Non	Reflex	441.00	9.70°	-57.80°	Non
Reflex	345.00	7.60°	-57.90°	Non	Reflex	444.00	10.30°	-57.90°	Non
Reflex	348.00	6.20°	-57.90°	Oui	Reflex	447.00	10.90°	-57.90°	Non
Reflex	351.00	8.40°	-58.00°	Non					
Reflex	354.00	8.10°	-58.00°	Non					
Reflex	357.00	8.70°	-57.90°	Non					
Reflex	360.00	6.50°	-58.00°	Non					
Reflex	363.00	5.90°	-58.00°	Non					
Reflex	366.00	6.20°	-57.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.80	MT						
		<b>Mort-terrain</b>						
3.80	447.21	SY; POR	3.80	5.00	D014204	1.20	<0.005	0.001
		<b>Syénite; Porphyrique</b>						
		Syénite porphyrique localement séricitisée, localement hématisée, parfois fortement carbonatée et magnétique.						
			5.00	6.50	D014206	1.50	0.005	0.005
			6.50	8.00	D014207	1.50	<0.005	0.001
			8.00	9.50	D014208	1.50	<0.005	0.001
			9.50	11.00	D014209	1.50	<0.005	0.001
			11.00	12.50	D014210	1.50	<0.005	0.001
			12.50	14.00	D014211	1.50	0.013	0.013
			14.00	15.50	D014212	1.50	<0.005	0.001
			15.50	17.00	D014213	1.50	0.027	0.027
			17.00	18.70	D014214	1.70	0.102	0.102
			18.70	20.00	D014216	1.30	0.464	0.464
			20.00	21.50	D014217	1.50	0.032	0.032
			21.50	23.00	D014218	1.50	0.177	0.177
			23.00	24.50	D014219	1.50	0.014	0.014
			24.50	26.00	D014220	1.50	0.064	0.064
			26.00	27.50	D014221	1.50	0.107	0.107
			27.50	29.00	D014222	1.50	0.015	0.015
			29.00	30.50	D014223	1.50	0.021	0.021
			30.50	32.00	D014224	1.50	0.051	0.051
			32.00	33.50	D014226	1.50	0.006	0.006
			33.50	35.00	D014227	1.50	0.006	0.006
			35.00	36.50	D014228	1.50	0.029	0.029
			36.50	38.00	D014229	1.50	0.011	0.011
			38.00	39.50	D014230	1.50	<0.005	0.001
			39.50	41.00	D014231	1.50	0.027	0.027
			41.00	42.50	D014232	1.50	0.044	0.044
			42.50	44.00	D014233	1.50	0.093	0.093
			44.00	45.50	D014234	1.50	0.089	0.089
			45.50	47.00	D014236	1.50	0.010	0.010
			47.00	48.50	D014237	1.50	0.006	0.006
			48.50	50.00	D014238	1.50	0.009	0.009
			50.00	51.50	D014239	1.50	0.036	0.036

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	51.50	53.00	D014241	1.50	0.013		0.013
	53.00	54.50	D014242	1.50	0.023		0.023
	54.50	56.00	D014243	1.50	0.011		0.011
	56.00	57.00	D014244	1.00	0.005		0.005
	57.00	58.50	D014246	1.50	0.064		0.064
	58.50	60.00	D014247	1.50	0.011		0.011
	60.00	61.50	D014248	1.50	0.012		0.012
	61.50	63.00	D014249	1.50	0.022		0.022
	63.00	64.50	D014250	1.50	0.041		0.041
	64.50	66.00	D014251	1.50	0.010		0.010
	66.00	67.50	D014252	1.50	0.020		0.020
	67.50	69.00	D014253	1.50	0.053		0.053
	69.00	70.50	D014254	1.50	0.035		0.035
	70.50	72.00	D014256	1.50	<0.005		0.001
	72.00	73.50	D014257	1.50	0.021		0.021
	73.50	75.00	D014258	1.50	0.207		0.207
	75.00	76.50	D014259	1.50	0.199		0.199
	76.50	78.00	D014260	1.50	<0.005		0.001
	78.00	79.50	D014261	1.50	0.010		0.010
	79.50	81.00	D014262	1.50	0.023		0.023
	81.00	82.50	D014263	1.50	0.014		0.014
	82.50	84.00	D014264	1.50	0.008		0.008
	84.00	85.50	D014266	1.50	0.017		0.017
	85.50	87.00	D014267	1.50	0.043		0.043
	87.00	88.50	D014268	1.50	0.114		0.114
	88.50	90.00	D014269	1.50	0.142		0.142
	90.00	91.50	D014270	1.50	0.090		0.090
	91.50	93.00	D014271	1.50	0.080		0.080
	93.00	94.00	D014272	1.00	0.016		0.016
	94.00	95.50	D014273	1.50	0.226		0.226
	95.50	97.00	D014274	1.50	2.700		2.700
	97.00	98.00	D014276	1.00	3.300		3.300
	98.00	99.00	D014277	1.00	2.600		2.600

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	99.00	100.50	D014278	1.50	0.278		0.278
	100.50	102.00	D014279	1.50	0.188		0.188
	102.00	103.50	D014281	1.50	0.177		0.177
	103.50	105.00	D014282	1.50	0.031		0.031
	105.00	106.30	D014283	1.30	0.016		0.016
	106.30	108.00	D014284	1.70	0.042		0.042
	108.00	109.50	D014286	1.50	0.057		0.057
	109.50	111.00	D014287	1.50	0.209		0.209
	111.00	112.50	D014288	1.50	0.035		0.035
	112.50	114.00	D014289	1.50	0.085		0.085
	114.00	115.50	D014290	1.50	0.306		0.306
	115.50	117.00	D014291	1.50	0.261		0.261
	117.00	118.20	D014292	1.20	0.071		0.071
	118.20	119.90	D014293	1.70	0.920		0.920
	119.90	121.50	D014294	1.60	0.077		0.077
	121.50	123.00	D014296	1.50	0.007		0.007
	123.00	124.50	D014297	1.50	0.005		0.005
	124.50	126.00	D014298	1.50	0.036		0.036
	126.00	127.50	D014299	1.50	0.011		0.011
	127.50	129.00	D014300	1.50	0.027		0.027
	129.00	130.50	D014301	1.50	0.021		0.021
	130.50	132.00	D014302	1.50	0.032		0.032
	132.00	133.00	D014303	1.00	0.060		0.060
	133.00	134.00	D014304	1.00	0.013		0.013
	134.00	135.50	D014306	1.50	0.129		0.129
	135.50	137.00	D014307	1.50	0.071		0.071
	137.00	138.50	D014308	1.50	0.007		0.007
	138.50	140.00	D014309	1.50	0.006		0.006
	140.00	141.50	D014310	1.50	0.016		0.016
	141.50	143.00	D014311	1.50	0.020		0.020
	143.00	144.50	D014312	1.50	0.006		0.006
	144.50	146.00	D014313	1.50	0.005		0.005
	146.00	147.50	D014314	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.50	149.00	D014316	1.50	0.005		0.005
	149.00	150.50	D014317	1.50	0.005		0.005
	150.50	152.00	D014318	1.50	0.038		0.038
	152.00	153.50	D014319	1.50	0.077		0.077
	153.50	155.00	D014321	1.50	0.016		0.016
	155.00	156.50	D014322	1.50	0.011		0.011
	156.50	158.00	D014323	1.50	0.022		0.022
	158.00	159.50	D014324	1.50	0.127		0.127
	159.50	161.00	D014326	1.50	<0.005		0.001
	161.00	162.50	D014327	1.50	0.077		0.077
	162.50	164.00	D014328	1.50	0.012		0.012
	164.00	165.50	D014329	1.50	0.014		0.014
	165.50	167.00	D014330	1.50	<0.005		0.001
	167.00	168.50	D014331	1.50	0.012		0.012
	168.50	170.00	D014332	1.50	0.010		0.010
	170.00	171.70	D014333	1.70	0.006		0.006
	171.70	173.40	D014334	1.70	0.012		0.012
	173.40	175.00	D014336	1.60	0.020		0.020
	175.00	176.00	D014337	1.00	0.012		0.012
	176.00	177.50	D014338	1.50	0.007		0.007
	177.50	179.00	D014339	1.50	0.024		0.024
	179.00	180.00	D014340	1.00	0.006		0.006
	180.00	181.50	D014341	1.50	0.106		0.106
	181.50	183.00	D014342	1.50	0.046		0.046
	183.00	184.50	D014343	1.50	0.030		0.030
	184.50	186.00	D014344	1.50	0.005		0.005
	186.00	187.50	D014346	1.50	<0.005		0.001
	187.50	189.00	D014347	1.50	<0.005		0.001
	189.00	190.50	D014348	1.50	0.009		0.009
	190.50	192.00	D014349	1.50	<0.005		0.001
	192.00	193.40	D014350	1.40	0.069		0.069
	193.40	195.00	D014351	1.60	0.130		0.130
	195.00	196.50	D014352	1.50	0.006		0.006



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	196.50	198.00	D014353	1.50	0.005		0.005
	198.00	199.50	D014354	1.50	0.464		0.464
	199.50	201.00	D014356	1.50	3.510		3.510
	201.00	202.50	D014357	1.50	0.054		0.054
	202.50	204.00	D014358	1.50	0.005		0.005
	204.00	205.50	D014359	1.50	0.005		0.005
	205.50	207.00	D014361	1.50	<0.005		0.001
	207.00	208.50	D014362	1.50	<0.005		0.001
	208.50	210.00	D014363	1.50	<0.005		0.001
	210.00	211.50	D014364	1.50	0.014		0.014
	211.50	213.00	D014366	1.50	0.013		0.013
	213.00	214.50	D014367	1.50	0.016		0.016
	214.50	216.00	D014368	1.50	0.112		0.112
	216.00	217.50	D014369	1.50	0.348		0.348
	217.50	219.00	D014370	1.50	0.802		0.802
	219.00	220.50	D014371	1.50	0.084		0.084
	220.50	222.00	D014372	1.50	0.040		0.040
	222.00	223.50	D014373	1.50	<0.005		0.001
	223.50	225.00	D014374	1.50	<0.005		0.001
	225.00	226.50	D014376	1.50	0.007		0.007
	226.50	228.00	D014377	1.50	<0.005		0.001
	228.00	229.50	D014378	1.50	0.088		0.088
	229.50	231.00	D014379	1.50	<0.005		0.001
	231.00	232.50	D014380	1.50	<0.005		0.001
	232.50	234.00	D014381	1.50	<0.005		0.001
	234.00	235.70	D014382	1.70	0.005		0.005
	235.70	236.70	D014383	1.00	0.096		0.096
	236.70	238.00	D014384	1.30	0.022		0.022
	238.00	239.50	D014386	1.50	0.022		0.022
	239.50	241.00	D014387	1.50	0.005		0.005
	241.00	242.50	D014388	1.50	<0.005		0.001
	242.50	244.00	D014389	1.50	0.005		0.005
	244.00	245.50	D014390	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	245.50	247.00	D014391	1.50	<0.005		0.001
	247.00	248.50	D014392	1.50	0.021		0.021
	248.50	250.00	D014393	1.50	0.008		0.008
	250.00	251.50	D014394	1.50	0.009		0.009
	251.50	253.00	D014396	1.50	0.017		0.017
	253.00	254.50	D014397	1.50	0.046		0.046
	254.50	256.00	D014398	1.50	<0.005		0.001
	256.00	257.50	D014399	1.50	0.005		0.005
	257.50	259.00	D014401	1.50	0.006		0.006
	259.00	260.00	D014402	1.00	0.569		0.569
	260.00	261.10	D014403	1.10	0.634		0.634
	261.10	262.40	D014404	1.30	0.012		0.012
	262.40	264.00	D014406	1.60	<0.005		0.001
	264.00	265.50	D014407	1.50	<0.005		0.001
	265.50	267.00	D014408	1.50	0.006		0.006
	267.00	268.50	D014409	1.50	<0.005		0.001
	268.50	270.00	D014410	1.50	<0.005		0.001
	270.00	271.50	D014411	1.50	<0.005		0.001
	271.50	273.00	D014412	1.50	0.022		0.022
	273.00	274.50	D014413	1.50	0.006		0.006
	274.50	276.00	D014414	1.50	<0.005		0.001
	276.00	277.50	D014416	1.50	0.033		0.033
	277.50	279.00	D014417	1.50	0.018		0.018
	279.00	280.50	D014418	1.50	<0.005		0.001
	280.50	282.00	D014419	1.50	<0.005		0.001
	282.00	283.50	D014420	1.50	0.105		0.105
	283.50	285.00	D014421	1.50	0.017		0.017
	285.00	286.50	D014422	1.50	0.121		0.121
	286.50	288.00	D014423	1.50	0.008		0.008
	288.00	289.50	D014424	1.50	0.017		0.017
	289.50	291.00	D014426	1.50	0.006		0.006
	291.00	292.50	D014427	1.50	<0.005		0.001
	292.50	294.00	D014428	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	294.00	295.50	D014429	1.50	<0.005		0.001
	295.50	297.00	D014430	1.50	<0.005		0.001
	297.00	298.50	D014431	1.50	<0.005		0.001
	298.50	300.00	D014432	1.50	<0.005		0.001
	300.00	301.50	D014433	1.50	<0.005		0.001
	301.50	303.00	D014434	1.50	0.005		0.005
	303.00	304.50	D014436	1.50	<0.005		0.001
	304.50	306.00	D014437	1.50	0.030		0.030
	306.00	307.50	D014438	1.50	0.021		0.021
	307.50	309.00	D014439	1.50	0.035		0.035
	309.00	310.00	D014441	1.00	0.287		0.287
	310.00	311.50	D014442	1.50	0.065		0.065
	311.50	313.00	D014443	1.50	<0.005		0.001
	313.00	314.50	D014444	1.50	0.150		0.150
	314.50	316.00	D014446	1.50	0.097		0.097
	316.00	317.00	D014447	1.00	0.084		0.084
	317.00	318.00	D014448	1.00	1.895		1.895
	318.00	319.60	D014449	1.60	0.079		0.079
	319.60	321.00	D014450	1.40	0.012		0.012
	321.00	322.50	D014451	1.50	0.021		0.021
	322.50	324.00	D014452	1.50	0.006		0.006
	324.00	325.50	D014453	1.50	0.014		0.014
	325.50	327.00	D014454	1.50	0.007		0.007
	327.00	328.50	D014456	1.50	0.006		0.006
	328.50	330.00	D014457	1.50	<0.005		0.001
	330.00	331.50	D014458	1.50	<0.005		0.001
	331.50	333.00	D014459	1.50	<0.005		0.001
	333.00	334.50	D014460	1.50	0.010		0.010
	334.50	336.00	D014461	1.50	<0.005		0.001
	336.00	337.50	D014462	1.50	0.006		0.006
	337.50	339.00	D014463	1.50	0.006		0.006
	339.00	340.50	D014464	1.50	<0.005		0.001
	340.50	342.00	D014466	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	342.00	343.50	D014467	1.50	0.008		0.008
	343.50	345.00	D014468	1.50	0.217		0.217
	345.00	346.50	D014469	1.50	0.041		0.041
	346.50	348.00	D014470	1.50	0.007		0.007
	348.00	349.50	D014471	1.50	0.015		0.015
	349.50	351.00	D014472	1.50	0.010		0.010
	351.00	352.50	D014473	1.50	0.039		0.039
	352.50	354.00	D014474	1.50	0.047		0.047
	354.00	355.50	D014476	1.50	<0.005		0.001
	355.50	357.00	D014477	1.50	0.134		0.134
	357.00	358.50	D014478	1.50	0.060		0.060
	358.50	360.00	D014479	1.50	0.504		0.504
	360.00	361.50	D014481	1.50	0.084		0.084
	361.50	363.00	D014482	1.50	0.247		0.247
	363.00	364.50	D014483	1.50	0.591		0.591
	364.50	366.00	D014484	1.50	0.649		0.649
	366.00	367.50	D014486	1.50	0.381		0.381
	367.50	369.00	D014487	1.50	0.015		0.015
	369.00	370.50	D014488	1.50	0.028		0.028
	370.50	372.00	D014489	1.50	0.375		0.375
	372.00	373.50	D014490	1.50	0.006		0.006
	373.50	375.00	D014491	1.50	<0.005		0.001
	375.00	376.50	D014492	1.50	0.006		0.006
	376.50	378.00	D014493	1.50	<0.005		0.001
	378.00	379.50	D014494	1.50	<0.005		0.001
	379.50	381.00	D014496	1.50	<0.005		0.001
	381.00	382.50	D014497	1.50	0.014		0.014
	382.50	384.00	D014498	1.50	<0.005		0.001
	384.00	385.50	D014499	1.50	0.006		0.006
	385.50	387.00	D014500	1.50	0.011		0.011
	387.00	388.50	D014501	1.50	0.018		0.018
	388.50	390.00	D014502	1.50	0.133		0.133
	390.00	391.50	D014503	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	391.50	393.00	D014504	1.50	0.247		0.247
	393.00	394.50	D014506	1.50	0.311		0.311
	394.50	396.00	D014507	1.50	0.472		0.472
	396.00	397.50	D014508	1.50	0.253		0.253
	397.50	399.00	D014509	1.50	0.507		0.507
	399.00	400.50	D014510	1.50	0.402		0.402
	400.50	402.00	D014511	1.50	0.022		0.022
	402.00	403.50	D014512	1.50	0.021		0.021
	403.50	405.00	D014513	1.50	0.056		0.056
	405.00	406.50	D014514	1.50	0.023		0.023
	406.50	408.00	D014516	1.50	0.027		0.027
	408.00	409.50	D014517	1.50	0.008		0.008
	409.50	411.00	D014518	1.50	0.020		0.020
	411.00	412.50	D014519	1.50	0.008		0.008
	412.50	414.00	D014521	1.50	0.078		0.078
	414.00	415.50	D014522	1.50	0.295		0.295
	415.50	417.00	D014523	1.50	0.013		0.013
	417.00	418.50	D014524	1.50	0.131		0.131
	418.50	420.00	D014526	1.50	0.031		0.031
	420.00	421.50	D014527	1.50	0.027		0.027
	421.50	423.00	D014528	1.50	0.012		0.012
	423.00	424.40	D014529	1.40	0.072		0.072
	424.40	426.00	D014530	1.60	0.653		0.653
	426.00	427.50	D014531	1.50	0.296		0.296
	427.50	429.00	D014532	1.50	0.320		0.320
	429.00	430.50	D014533	1.50	0.863		0.863
	430.50	432.00	D014534	1.50	0.153		0.153
	432.00	433.50	D014536	1.50	0.451		0.451
	433.50	435.00	D014537	1.50	0.149		0.149
	435.00	436.50	D014538	1.50	0.301		0.301
	436.50	438.00	D014539	1.50	0.788		0.788
	438.00	439.50	D014540	1.50	0.325		0.325
	439.50	441.00	D014541	1.50	0.924		0.924

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	441.00	442.50	D014542	1.50	0.205		0.205
	442.50	444.00	D014543	1.50	0.510		0.510
	444.00	445.00	D014544	1.00	0.900		0.900
	445.00	446.00	D014546	1.00	0.355		0.355
	446.00	447.20	D014547	1.20	0.596		0.596
<p>447.21 Fin du sondage            Nombre d'échantillons : 301            Nombre d'échantillons QAQC : 43            Longueur totale échantillonnée : 443.40</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
3.80	5.00	D014205	D014204	1.20	0.006	0.006
17.00	17.00	D014215	C4	0.00	1.360	1.360
30.50	32.00	D014225	D014224	1.50	0.011	0.011
44.00	44.00	D014235	D2	0.00	0.863	0.863
50.00	50.00	D014240	M1	0.00	<0.005	0.001
56.00	57.00	D014245	D014244	1.00	0.007	0.007
69.00	69.00	D014255	G2	0.00	3.920	3.920
82.50	84.00	D014265	D014264	1.50	0.013	0.013
95.50	95.50	D014275	H	0.00	0.950	0.950
100.50	100.50	D014280	M1	0.00	0.007	0.007
106.30	108.00	D014285	D014284	1.70	0.041	0.041
119.90	119.90	D014295	A3	0.00	0.599	0.599
133.00	134.00	D014305	D014304	1.00	0.006	0.006
146.00	146.00	D014315	B4	0.00	2.690	2.690
152.00	152.00	D014320	M1	0.00	<0.005	0.001
158.00	159.50	D014325	D014324	1.50	0.064	0.064
171.70	171.70	D014335	C4	0.00	1.410	1.410
184.50	186.00	D014345	D014344	1.50	0.010	0.010
198.00	198.00	D014355	D2	0.00	0.832	0.832
204.00	204.00	D014360	M1	0.00	0.006	0.006
210.00	211.50	D014365	D014364	1.50	0.013	0.013
223.50	223.50	D014375	G2	0.00	4.070	4.070
236.70	238.00	D014385	D014384	1.30	0.022	0.022
250.00	250.00	D014395	H	0.00	0.980	0.980
256.00	256.00	D014400	M1	0.00	0.006	0.006
261.10	262.40	D014405	D014404	1.30	0.013	0.013
274.50	274.50	D014415	A3	0.00	0.480	0.480
288.00	289.50	D014425	D014424	1.50	0.012	0.012
301.50	301.50	D014435	B4	0.00	2.670	2.670
307.50	307.50	D014440	M1	0.00	<0.005	0.001
313.00	314.50	D014445	D014444	1.50	0.212	0.212
325.50	325.50	D014455	C4	0.00	1.380	1.380
339.00	340.50	D014465	D014464	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
352.50	352.50	D014475	D2	0.00	0.866	0.866
358.50	358.50	D014480	M1	0.00	<0.005	0.001
364.50	366.00	D014485	D014484	1.50	0.612	0.612
378.00	378.00	D014495	G2	0.00	4.050	4.050
391.50	393.00	D014505	D014504	1.50	0.222	0.222
405.00	405.00	D014515	H	0.00	0.978	0.978
411.00	411.00	D014520	M1	0.00	<0.005	0.001
417.00	418.50	D014525	D014524	1.50	0.131	0.131
430.50	430.50	D014535	A3	0.00	0.625	0.625
444.00	445.00	D014545	D014544	1.00	0.919	0.919



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-175**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-05-07

Date de description :

Au :                      2010-05-08

Collet

UTM

Azimut :                      0.00°

Plongée :                      -45.00°

Longueur :                      110.00 m

Est                              629 899.8

Nord                              5 374 451.9

Élévation                      280.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	0.00°	0.00°	Oui
Reflex	11.00	347.50°	-45.40°	Oui
Reflex	14.00	343.50°	-44.90°	Oui
Reflex	17.00	350.80°	-44.70°	Oui
Reflex	20.00	353.50°	-45.10°	Oui
Reflex	23.00	343.80°	-45.20°	Oui
Reflex	26.00	348.70°	-45.00°	Oui
Reflex	29.00	357.50°	-44.80°	Oui
Reflex	32.00	346.50°	-44.90°	Oui
Reflex	35.00	334.10°	-45.00°	Oui
Reflex	38.00	342.90°	-45.30°	Oui
Reflex	41.00	289.00°	-45.50°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	353.00°	-45.40°	Oui
Reflex	47.00	357.50°	-45.40°	Non
Reflex	50.00	358.00°	-45.40°	Non
Reflex	53.00	358.30°	-45.50°	Non
Reflex	56.00	358.30°	-45.40°	Non
Reflex	59.00	358.20°	-45.30°	Non
Reflex	62.00	358.00°	-45.10°	Non
Reflex	65.00	357.90°	-45.00°	Non
Reflex	68.00	357.90°	-44.80°	Non
Reflex	71.00	358.10°	-44.70°	Non
Reflex	74.00	357.90°	-44.50°	Non
Reflex	77.00	357.90°	-44.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	357.90°	-44.40°	Non					
Reflex	83.00	358.10°	-44.30°	Non					
Reflex	86.00	358.20°	-44.20°	Non					
Reflex	89.00	358.30°	-44.20°	Non					
Reflex	92.00	358.50°	-44.20°	Non					
Reflex	95.00	358.70°	-44.10°	Non					
Reflex	98.00	358.80°	-44.10°	Non					
Reflex	101.00	358.80°	-44.10°	Non					
Reflex	104.00	358.90°	-44.10°	Non					
Reflex	107.00	359.00°	-44.10°	Non					
Reflex	110.00	358.20°	-44.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	45.00	MT						
		<b>Mort-terrain</b>						
45.00	76.50	BA; MAS; AMY; COU	45.00	46.50	D017330	1.50	0.436	0.436
		<b>Basalte; Roche massive; Amygdalaire; Coussiné</b>	46.50	48.00	D017331	1.50	0.005	0.005
		Basalte massif avec passage amygdalaire et coussiné.	48.00	49.50	D017332	1.50	0.005	0.005
			49.50	51.00	D017333	1.50	0.015	0.015
			51.00	52.50	D017334	1.50	6.140	6.140
			52.50	54.00	D017335	1.50	0.024	0.024
			54.00	55.50	D017336	1.50	0.012	0.012
			55.50	57.00	D017338	1.50	0.007	0.007
			57.00	58.50	D017339	1.50	<0.005	0.001
			58.50	60.00	D017340	1.50	0.005	0.005
			60.00	61.50	D017341	1.50	0.005	0.005
			61.50	63.00	D017342	1.50	<0.005	0.001
			63.00	64.50	D017343	1.50	<0.005	0.001
			64.50	66.00	D017344	1.50	0.005	0.005
			66.00	67.50	D017345	1.50	0.006	0.006
			67.50	69.00	D017346	1.50	0.005	0.005
			69.00	70.50	D017348	1.50	<0.005	0.001
			70.50	72.00	D017349	1.50	<0.005	0.001
			72.00	73.50	D017350	1.50	0.006	0.006
			73.50	75.00	D017351	1.50	<0.005	0.001
			75.00	76.50	D017352	1.50	<0.005	0.001
76.50	110.00	GA; FIN; MTY; POR	76.50	78.00	D017353	1.50	<0.005	0.001
		<b>Gabbro; Grains fins; Grains moyens; Porphyrique</b>	78.00	79.50	D017354	1.50	<0.005	0.001
		Gabbro, à grains fins à moyens avec passage porphyrique.	79.50	81.00	D017355	1.50	<0.005	0.001
			81.00	82.50	D017356	1.50	0.006	0.006
			82.50	84.00	D017358	1.50	<0.005	0.001
			84.00	85.50	D017359	1.50	<0.005	0.001
			85.50	87.00	D017360	1.50	<0.005	0.001
			87.00	88.50	D017361	1.50	<0.005	0.001
			88.50	90.00	D017363	1.50	<0.005	0.001
			90.00	91.50	D017364	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	91.50	93.00	D017365	1.50	<0.005		0.001
	93.00	94.50	D017366	1.50	<0.005		0.001
	94.50	96.00	D017368	1.50	<0.005		0.001
	96.00	97.50	D017369	1.50	<0.005		0.001
	97.50	99.00	D017370	1.50	<0.005		0.001
	99.00	100.50	D017371	1.50	<0.005		0.001
	100.50	102.00	D017372	1.50	<0.005		0.001
	102.00	103.50	D017373	1.50	<0.005		0.001
	103.50	105.00	D017374	1.50	<0.005		0.001
	105.00	106.50	D017375	1.50	<0.005		0.001
	106.50	108.00	D017376	1.50	<0.005		0.001
	108.00	109.00	D017378	1.00	<0.005		0.001
	109.00	110.00	D017379	1.00	<0.005		0.001
110.00	Fin du sondage Nombre d'échantillons : 44 Nombre d'échantillons QAQC : 6 Longueur totale échantillonnée : 65.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
54.00	55.50	D017337	D017336	1.50	0.008	0.008
67.50	69.00	D017347	D2	1.50	0.842	0.842
81.00	82.50	D017357	D017356	1.50	<0.005	0.001
87.00	88.50	D017362	M1	1.50	<0.005	0.001
93.00	94.50	D017367	C4	1.50	1.350	1.350
106.50	108.00	D017377	D017376	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-176**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy Gbaguidi

Lot :

Du :                      2010-05-08

Date de description :

Au :                      2010-05-10

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      166.80 m

Est	629 899.6
Nord	5 374 451.5
Élévation	280.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	337.50°	-60.70°	Oui
Reflex	8.00	337.60°	-60.60°	Oui
Reflex	11.00	336.20°	-60.90°	Oui
Reflex	14.00	357.30°	-60.30°	Oui
Reflex	17.00	357.00°	-60.10°	Oui
Reflex	20.00	36.50°	-60.30°	Oui
Reflex	23.00	335.40°	-60.10°	Oui
Reflex	26.00	311.20°	-60.00°	Oui
Reflex	29.00	314.50°	-60.10°	Oui
Reflex	32.00	355.90°	-60.40°	Non
Reflex	35.00	356.20°	-60.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.70°	-60.20°	Non
Reflex	41.00	359.00°	-60.10°	Non
Reflex	44.00	359.00°	-59.90°	Non
Reflex	47.00	359.00°	-59.70°	Non
Reflex	50.00	359.00°	-59.70°	Non
Reflex	53.00	359.10°	-59.50°	Non
Reflex	56.00	359.30°	-59.40°	Non
Reflex	59.00	359.20°	-59.40°	Non
Reflex	62.00	359.20°	-59.30°	Non
Reflex	65.00	359.30°	-59.10°	Non
Reflex	68.00	356.80°	-56.10°	Non
Reflex	71.00	359.00°	-58.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.00°	-58.80°	Non					
Reflex	77.00	359.10°	-58.90°	Non					
Reflex	80.00	358.80°	-58.10°	Non					
Reflex	83.00	359.10°	-58.70°	Non					
Reflex	86.00	359.00°	-58.60°	Non					
Reflex	89.00	358.80°	-58.60°	Non					
Reflex	92.00	358.90°	-58.60°	Non					
Reflex	95.00	359.00°	-58.60°	Non					
Reflex	98.00	358.90°	-58.50°	Non					
Reflex	101.00	358.90°	-58.40°	Non					
Reflex	104.00	359.00°	-58.60°	Non					
Reflex	107.00	358.90°	-58.30°	Non					
Reflex	110.00	358.80°	-58.20°	Non					
Reflex	113.00	358.80°	-58.10°	Non					
Reflex	116.00	358.90°	-58.00°	Non					
Reflex	119.00	358.80°	-57.90°	Non					
Reflex	122.00	358.80°	-57.80°	Non					
Reflex	125.00	358.80°	-57.70°	Non					
Reflex	128.00	358.80°	-57.60°	Non					
Reflex	131.00	359.00°	-57.60°	Non					
Reflex	134.00	359.00°	-57.50°	Non					
Reflex	137.00	358.90°	-57.50°	Non					
Reflex	140.00	359.10°	-57.50°	Non					
Reflex	143.00	359.10°	-57.50°	Non					
Reflex	146.00	359.10°	-57.50°	Non					
Reflex	149.00	359.30°	-57.50°	Non					
Reflex	152.00	359.40°	-57.50°	Non					
Reflex	155.00	359.40°	-57.30°	Non					
Reflex	158.00	359.30°	-57.30°	Non					
Reflex	161.00	359.30°	-57.20°	Non					
Reflex	164.00	359.40°	-57.20°	Non					
Reflex	166.80	359.50°	-57.00°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	33.00	MT <b>Mort-terrain</b>						
33.00	53.00	GA <b>Gabbro</b> Gabbro à leucocène massive fortement carbonaté.	33.00	34.50	D014548	1.50	<0.005	0.001
			34.50	36.00	D014549	1.50	<0.005	0.001
			36.00	37.50	D014550	1.50	<0.005	0.001
			37.50	39.00	D014551	1.50	<0.005	0.001
			39.00	40.50	D014552	1.50	<0.005	0.001
			40.50	42.00	D014553	1.50	<0.005	0.001
			42.00	43.50	D014554	1.50	<0.005	0.001
			43.50	45.00	D014556	1.50	<0.005	0.001
			45.00	46.50	D014557	1.50	<0.005	0.001
			46.50	48.00	D014558	1.50	<0.005	0.001
			48.00	49.50	D014559	1.50	<0.005	0.001
			49.50	51.00	D014561	1.50	<0.005	0.001
			51.00	52.00	D014562	1.00	<0.005	0.001
			52.00	53.00	D014563	1.00	<0.005	0.001
53.00	123.50	BA; AMY <b>Basalte 20°; Amygdalaire</b> basalte massive, localement amygdalaire, bréchifié par endroit, parfois complètement remplacé.	53.00	54.50	D014564	1.50	0.009	0.009
			54.50	56.00	D014566	1.50	0.006	0.006
			56.00	57.50	D014567	1.50	0.006	0.006
			57.50	59.00	D014568	1.50	0.180	0.180
			59.00	60.50	D014569	1.50	0.336	0.336
			60.50	62.00	D014570	1.50	<0.005	0.001
			62.00	63.50	D014571	1.50	0.005	0.005
			63.50	65.00	D014572	1.50	0.006	0.006
			65.00	66.50	D014573	1.50	0.005	0.005
			66.50	68.00	D014574	1.50	<0.005	0.001
			68.00	69.50	D014576	1.50	<0.005	0.001
			69.50	71.00	D014577	1.50	<0.005	0.001
			71.00	72.50	D014578	1.50	0.006	0.006
			72.50	74.00	D014579	1.50	<0.005	0.001
			74.00	75.50	D014580	1.50	0.009	0.009
			75.50	77.00	D014581	1.50	0.319	0.319
			77.00	78.00	D014582	1.00	0.005	0.005



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	78.00	79.00	D014583	1.00	0.310		0.310	
	79.00	80.10	D014584	1.10	3.080		3.080	
	80.10	81.50	D014586	1.40	0.044		0.044	
	81.50	83.00	D014587	1.50	0.056		0.056	
	83.00	84.50	D014588	1.50	<0.005		0.001	
	84.50	86.00	D014589	1.50	0.005		0.005	
	86.00	87.50	D014590	1.50	0.005		0.005	
	87.50	89.00	D014591	1.50	<0.005		0.001	
	89.00	90.50	D014592	1.50	<0.005		0.001	
	90.50	92.00	D014593	1.50	<0.005		0.001	
	92.00	93.50	D014594	1.50	<0.005		0.001	
	93.50	95.00	D014596	1.50	<0.005		0.001	
	95.00	96.50	D014597	1.50	<0.005		0.001	
	96.50	98.00	D014598	1.50	<0.005		0.001	
	98.00	99.50	D014599	1.50	0.007		0.007	
	99.50	101.00	D014601	1.50	<0.005		0.001	
	101.00	102.50	D014602	1.50	0.005		0.005	
	102.50	104.00	D014603	1.50	<0.005		0.001	
	104.00	105.50	D014604	1.50	<0.005		0.001	
	105.50	107.00	D014606	1.50	0.007		0.007	
	107.00	108.50	D014607	1.50	<0.005		0.001	
	108.50	110.00	D014608	1.50	<0.005		0.001	
	110.00	111.50	D014609	1.50	0.005		0.005	
	111.50	113.00	D014610	1.50	0.020		0.020	
	113.00	114.50	D014611	1.50	0.005		0.005	
	114.50	116.00	D014612	1.50	<0.005		0.001	
	116.00	117.50	D014613	1.50	0.007		0.007	
	117.50	119.00	D014614	1.50	0.005		0.005	
	119.00	120.50	D014616	1.50	0.005		0.005	
	120.50	122.00	D014617	1.50	<0.005		0.001	
	122.00	123.50	D014618	1.50	0.005		0.005	
123.50	166.80	GA	123.50	125.00	D014619	1.50	<0.005	0.001
		<b>Gabbro</b>	125.00	126.50	D014620	1.50	<0.005	0.001
		gabbro à leucocène carbonaté.						

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	126.50	128.00	D014621	1.50	0.006		0.006
	128.00	129.50	D014622	1.50	<0.005		0.001
	129.50	131.00	D014623	1.50	<0.005		0.001
	131.00	132.50	D014624	1.50	<0.005		0.001
	132.50	134.00	D014626	1.50	<0.005		0.001
	134.00	135.50	D014627	1.50	<0.005		0.001
	135.50	137.00	D014628	1.50	<0.005		0.001
	137.00	138.50	D014629	1.50	<0.005		0.001
	138.50	140.00	D014630	1.50	<0.005		0.001
	140.00	141.50	D014631	1.50	<0.005		0.001
	141.50	143.00	D014632	1.50	<0.005		0.001
	143.00	144.50	D014633	1.50	<0.005		0.001
	144.50	146.00	D014634	1.50	<0.005		0.001
	146.00	147.50	D014636	1.50	<0.005		0.001
	147.50	149.00	D014637	1.50	<0.005		0.001
	149.00	150.50	D014638	1.50	0.005		0.005
	150.50	152.00	D014639	1.50	<0.005		0.001
	152.00	153.70	D014641	1.70	<0.005		0.001
	153.70	155.40	D014642	1.70	0.032		0.032
	155.40	157.00	D014643	1.60	0.152		0.152
	157.00	158.50	D014644	1.50	1.715		1.715
	158.50	160.00	D014646	1.50	0.007		0.007
	160.00	161.50	D014647	1.50	0.010		0.010
	161.50	163.00	D014648	1.50	<0.005		0.001
	163.00	164.00	D014649	1.00	<0.005		0.001
	164.00	165.50	D014650	1.50	<0.005		0.001
	165.50	166.80	D014651	1.30	<0.005		0.001
166.80	Fin du sondage						
	Nombre d'échantillons : 91						
	Nombre d'échantillons QAQC : 13						
	Longueur totale échantillonnée : 133.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
42.00	42.00	D014555	B4	0.00	2.540	2.540
48.00	48.00	D014560	M1	0.00	<0.005	0.001
53.00	54.50	D014565	D014564	1.50	0.010	0.010
66.50	66.50	D014575	C4	0.00	1.305	1.305
79.00	80.10	D014585	D014584	1.10	3.440	3.440
92.00	92.00	D014595	D2	0.00	0.830	0.830
98.00	98.00	D014600	M1	0.00	<0.005	0.001
104.00	105.50	D014605	D014604	1.50	<0.005	0.001
117.50	117.50	D014615	G2	0.00	3.970	3.970
131.00	132.50	D014625	D014624	1.50	<0.005	0.001
144.50	144.50	D014635	H	0.00	0.998	0.998
150.50	150.50	D014640	M1	0.00	<0.005	0.001
157.00	158.50	D014645	D014644	1.50	2.060	2.060

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-177**

Titre minier :

Section :                      630300

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Guy Gbaguidi

Lot :

Du :                              2010-04-21

Date de description :

Au :                              2010-05-03

Collet

UTM

Azimut :                      3.00°  
 Plongée :                      -63.00°  
 Longueur :                      450.00 m

Est	630 296.1
Nord	5 374 222.1
Élévation	308.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	1.90°	-63.20°	Non
Reflex	9.00	1.60°	-63.20°	Non
Reflex	12.00	1.70°	-63.10°	Non
Reflex	15.00	2.60°	-63.00°	Oui
Reflex	18.00	1.80°	-62.90°	Non
Reflex	21.00	1.70°	-62.80°	Non
Reflex	24.00	1.10°	-62.70°	Non
Reflex	27.00	0.70°	-62.60°	Non
Reflex	30.00	359.80°	-62.50°	Non
Reflex	33.00	0.40°	-62.50°	Non
Reflex	36.00	360.00°	-62.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	0.60°	-62.50°	Non
Reflex	42.00	0.20°	-62.50°	Non
Reflex	45.00	0.40°	-62.50°	Non
Reflex	48.00	0.20°	-62.50°	Non
Reflex	51.00	359.90°	-62.50°	Non
Reflex	54.00	0.30°	-62.50°	Non
Reflex	57.00	359.60°	-62.50°	Non
Reflex	60.00	0.30°	-62.50°	Non
Reflex	63.00	0.40°	-62.60°	Non
Reflex	66.00	0.60°	-62.60°	Non
Reflex	69.00	1.30°	-62.60°	Non
Reflex	72.00	0.20°	-62.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	359.30°	-62.60°	Non
Reflex	78.00	0.20°	-62.60°	Non
Reflex	81.00	359.30°	-62.50°	Non
Reflex	84.00	358.50°	-62.50°	Non
Reflex	87.00	359.20°	-62.60°	Non
Reflex	90.00	0.70°	-62.60°	Non
Reflex	93.00	0.30°	-62.60°	Non
Reflex	96.00	0.90°	-62.60°	Non
Reflex	99.00	1.60°	-62.50°	Non
Reflex	102.00	1.60°	-62.50°	Non
Reflex	105.00	0.30°	-62.50°	Non
Reflex	108.00	0.40°	-62.50°	Non
Reflex	111.00	0.70°	-62.50°	Non
Reflex	114.00	0.50°	-62.50°	Non
Reflex	117.00	0.80°	-62.50°	Non
Reflex	120.00	0.60°	-62.50°	Non
Reflex	123.00	0.60°	-62.50°	Non
Reflex	126.00	0.90°	-62.40°	Non
Reflex	129.00	0.60°	-62.40°	Non
Reflex	132.00	1.10°	-62.40°	Non
Reflex	135.00	1.10°	-62.50°	Non
Reflex	138.00	1.30°	-62.50°	Non
Reflex	141.00	1.30°	-62.50°	Non
Reflex	144.00	0.80°	-62.50°	Non
Reflex	147.00	1.70°	-62.50°	Non
Reflex	150.00	1.70°	-62.50°	Non
Reflex	153.00	1.30°	-62.50°	Non
Reflex	156.00	1.60°	-62.50°	Non
Reflex	159.00	2.50°	-62.50°	Non
Reflex	162.00	1.40°	-62.50°	Non
Reflex	165.00	1.60°	-62.50°	Non
Reflex	168.00	358.40°	-62.50°	Oui
Reflex	171.00	0.40°	-62.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	174.00	1.00°	-62.60°	Non
Reflex	177.00	1.50°	-62.60°	Non
Reflex	180.00	357.10°	-62.60°	Non
Reflex	183.00	358.70°	-62.60°	Non
Reflex	186.00	0.40°	-62.60°	Non
Reflex	189.00	1.00°	-62.60°	Non
Reflex	192.00	357.30°	-62.60°	Non
Reflex	195.00	359.90°	-62.60°	Non
Reflex	198.00	2.20°	-62.60°	Oui
Reflex	201.00	3.40°	-62.60°	Oui
Reflex	204.00	358.20°	-62.60°	Non
Reflex	207.00	358.90°	-62.60°	Non
Reflex	210.00	2.30°	-62.50°	Non
Reflex	213.00	3.50°	-62.50°	Non
Reflex	216.00	3.80°	-62.50°	Non
Reflex	219.00	3.40°	-62.40°	Non
Reflex	222.00	2.50°	-62.30°	Non
Reflex	225.00	0.90°	-62.30°	Oui
Reflex	228.00	2.50°	-62.40°	Non
Reflex	231.00	1.50°	-62.40°	Oui
Reflex	234.00	3.40°	-62.40°	Non
Reflex	237.00	3.00°	-62.40°	Non
Reflex	240.00	3.20°	-62.40°	Non
Reflex	243.00	0.40°	-62.40°	Oui
Reflex	246.00	2.60°	-62.50°	Non
Reflex	249.00	3.60°	-62.40°	Non
Reflex	252.00	4.10°	-62.50°	Non
Reflex	255.00	4.00°	-62.50°	Non
Reflex	258.00	3.60°	-62.50°	Non
Reflex	261.00	4.20°	-62.50°	Non
Reflex	264.00	4.30°	-62.50°	Non
Reflex	267.00	3.90°	-62.50°	Non
Reflex	270.00	3.30°	-62.50°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	2.50°	-62.50°	Oui	Reflex	372.00	8.10°	-62.10°	Non
Reflex	276.00	4.00°	-62.50°	Non	Reflex	375.00	8.40°	-62.10°	Non
Reflex	279.00	3.70°	-62.50°	Non	Reflex	378.00	8.70°	-62.00°	Non
Reflex	282.00	5.30°	-62.50°	Oui	Reflex	381.00	7.10°	-62.00°	Oui
Reflex	285.00	4.90°	-62.50°	Non	Reflex	384.00	9.60°	-61.90°	Non
Reflex	288.00	5.20°	-62.60°	Non	Reflex	387.00	9.90°	-61.80°	Non
Reflex	291.00	5.50°	-62.60°	Non	Reflex	390.00	9.00°	-61.70°	Non
Reflex	294.00	5.10°	-62.60°	Non	Reflex	393.00	8.90°	-61.70°	Non
Reflex	297.00	3.90°	-62.60°	Oui	Reflex	396.00	7.80°	-61.70°	Non
Reflex	300.00	3.50°	-62.60°	Oui	Reflex	399.00	8.10°	-61.70°	Non
Reflex	303.00	5.80°	-62.60°	Non	Reflex	402.00	9.10°	-61.70°	Non
Reflex	306.00	5.20°	-62.60°	Non	Reflex	405.00	10.00°	-61.70°	Non
Reflex	309.00	5.60°	-62.60°	Non	Reflex	408.00	9.90°	-61.60°	Non
Reflex	312.00	4.80°	-62.60°	Non	Reflex	411.00	10.20°	-61.60°	Non
Reflex	315.00	4.70°	-62.60°	Non	Reflex	414.00	10.30°	-61.50°	Non
Reflex	318.00	5.80°	-62.60°	Non	Reflex	417.00	10.20°	-61.50°	Non
Reflex	321.00	5.20°	-62.70°	Non	Reflex	420.00	10.60°	-61.50°	Non
Reflex	324.00	6.50°	-62.70°	Non	Reflex	423.00	10.40°	-61.40°	Non
Reflex	327.00	6.10°	-62.70°	Non	Reflex	426.00	8.90°	-61.40°	Non
Reflex	330.00	6.10°	-62.70°	Non	Reflex	429.00	8.90°	-61.40°	Non
Reflex	333.00	6.10°	-62.60°	Non	Reflex	432.00	8.40°	-61.30°	Non
Reflex	336.00	6.00°	-62.60°	Non	Reflex	435.00	8.80°	-61.30°	Non
Reflex	339.00	6.80°	-62.60°	Non	Reflex	438.00	9.20°	-61.20°	Non
Reflex	342.00	7.60°	-62.50°	Non	Reflex	441.00	9.70°	-61.20°	Non
Reflex	345.00	9.30°	-62.50°	Non	Reflex	444.00	9.60°	-61.20°	Non
Reflex	348.00	6.80°	-62.40°	Non	Reflex	447.00	9.80°	-61.10°	Non
Reflex	351.00	6.40°	-62.40°	Non	Reflex	450.00	10.10°	-61.20°	Non
Reflex	354.00	7.50°	-62.30°	Non					
Reflex	357.00	8.90°	-62.30°	Non					
Reflex	360.00	7.40°	-62.30°	Non					
Reflex	363.00	6.60°	-62.20°	Non					
Reflex	366.00	8.20°	-62.20°	Non					
Reflex	369.00	8.70°	-62.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.00	MT						
		<b>Mort-terrain</b>						
1.00	450.00	SY; POR	1.00	2.50	D014652	1.50	0.014	0.014
		<b>Syénite; Porphyrique</b>	2.50	4.00	D014653	1.50	0.009	0.009
		Syénite porphyrique carbonatée, magnétique et hématisée.	4.00	5.50	D014654	1.50	0.021	0.021
			5.50	7.00	D014656	1.50	0.070	0.070
			7.00	8.50	D014657	1.50	0.009	0.009
			8.50	10.00	D014658	1.50	0.016	0.016
			10.00	11.50	D014659	1.50	0.075	0.075
			11.50	13.00	D014660	1.50	0.044	0.044
			13.00	14.50	D014661	1.50	0.225	0.225
			14.50	16.00	D014662	1.50	0.376	0.376
			16.00	17.50	D014663	1.50	0.267	0.267
			17.50	19.00	D014664	1.50	0.082	0.082
			19.00	20.50	D014666	1.50	0.312	0.312
			20.50	22.00	D014667	1.50	0.065	0.065
			22.00	23.50	D014668	1.50	0.006	0.006
			23.50	25.00	D014669	1.50	0.025	0.025
			25.00	26.50	D014670	1.50	<0.005	0.001
			26.50	28.00	D014671	1.50	<0.005	0.001
			28.00	29.50	D014672	1.50	<0.005	0.001
			29.50	31.00	D014673	1.50	0.007	0.007
			31.00	32.50	D014674	1.50	<0.005	0.001
			32.50	34.00	D014676	1.50	0.040	0.040
			34.00	35.50	D014677	1.50	0.016	0.016
			35.50	37.00	D014678	1.50	0.137	0.137
			37.00	38.50	D014679	1.50	0.134	0.134
			38.50	40.00	D014681	1.50	0.028	0.028
			40.00	41.50	D014682	1.50	0.080	0.080
			41.50	43.00	D014683	1.50	0.018	0.018
			43.00	44.50	D014684	1.50	<0.005	0.001
			44.50	46.00	D014686	1.50	0.006	0.006
			46.00	47.50	D014687	1.50	0.005	0.005
			47.50	49.00	D014688	1.50	0.011	0.011

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.00	50.50	D014689	1.50	0.027		0.027
	50.50	52.00	D014690	1.50	0.266		0.266
	52.00	53.50	D014691	1.50	0.105		0.105
	53.50	55.00	D014692	1.50	0.008		0.008
	55.00	56.50	D014693	1.50	0.009		0.009
	56.50	58.00	D014694	1.50	0.012		0.012
	58.00	59.50	D014696	1.50	0.006		0.006
	59.50	61.00	D014697	1.50	0.036		0.036
	61.00	62.50	D014698	1.50	0.008		0.008
	62.50	64.00	D014699	1.50	<0.005		0.001
	64.00	65.50	D014700	1.50	0.005		0.005
	65.50	67.00	D014701	1.50	<0.005		0.001
	67.00	68.50	D014702	1.50	0.007		0.007
	68.50	70.00	D014703	1.50	0.007		0.007
	70.00	71.50	D014704	1.50	<0.005		0.001
	71.50	73.00	D014706	1.50	<0.005		0.001
	73.00	74.50	D014707	1.50	2.400		2.400
	74.50	76.00	D014708	1.50	0.189		0.189
	76.00	77.50	D014709	1.50	0.806		0.806
	77.50	79.00	D014710	1.50	2.110		2.110
	79.00	80.50	D014711	1.50	1.370		1.370
	80.50	81.50	D014712	1.00	1.010		1.010
	81.50	83.20	D014713	1.70	5.370		5.370
	83.20	84.70	D014714	1.50	0.523		0.523
	84.70	86.20	D014716	1.50	0.464		0.464
	86.20	87.50	D014717	1.30	1.620		1.620
	87.50	89.00	D014718	1.50	0.116		0.116
	89.00	90.50	D014719	1.50	0.288		0.288
	90.50	92.00	D014721	1.50	0.019		0.019
	92.00	93.50	D014722	1.50	<0.005		0.001
	93.50	95.00	D014723	1.50	0.308		0.308
	95.00	96.50	D014724	1.50	0.641		0.641
	96.50	98.00	D014726	1.50	0.228		0.228



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.00	99.50	D014727	1.50	0.141		0.141
	99.50	101.00	D014728	1.50	0.378		0.378
	101.00	102.50	D014729	1.50	0.010		0.010
	102.50	104.00	D014730	1.50	0.005		0.005
	104.00	105.50	D014731	1.50	<0.005		0.001
	105.50	107.00	D014732	1.50	<0.005		0.001
	107.00	108.50	D014733	1.50	0.045		0.045
	108.50	110.00	D014734	1.50	<0.005		0.001
	110.00	111.50	D014736	1.50	<0.005		0.001
	111.50	113.00	D014737	1.50	<0.005		0.001
	113.00	114.50	D014738	1.50	<0.005		0.001
	114.50	116.00	D014739	1.50	<0.005		0.001
	116.00	117.50	D014740	1.50	<0.005		0.001
	117.50	119.00	D014741	1.50	<0.005		0.001
	119.00	120.50	D014742	1.50	0.005		0.005
	120.50	122.00	D014743	1.50	0.066		0.066
	122.00	123.50	D014744	1.50	0.005		0.005
	123.50	125.00	D014746	1.50	0.005		0.005
	125.00	126.50	D014747	1.50	<0.005		0.001
	126.50	128.00	D014748	1.50	<0.005		0.001
	128.00	129.50	D014749	1.50	0.031		0.031
	129.50	131.00	D014750	1.50	0.261		0.261
	131.00	132.50	D014751	1.50	0.018		0.018
	132.50	134.00	D014752	1.50	0.005		0.005
	134.00	135.50	D014753	1.50	0.018		0.018
	135.50	137.00	D014754	1.50	0.037		0.037
	137.00	138.50	D014756	1.50	0.013		0.013
	138.50	140.00	D014757	1.50	0.484		0.484
	140.00	141.50	D014758	1.50	0.013		0.013
	141.50	143.00	D014759	1.50	0.154		0.154
	143.00	144.50	D014760	1.50	0.037		0.037
	144.50	146.00	D014761	1.50	0.098		0.098
	146.00	147.50	D014762	1.50	0.036		0.036

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	147.50	149.00	D014763	1.50	0.076		0.076	
	149.00	150.50	D014764	1.50	0.291		0.291	
	150.50	152.00	D014766	1.50	0.049		0.049	
	152.00	153.50	D014767	1.50	0.098		0.098	
	153.50	155.00	D014768	1.50	0.158		0.158	
	155.00	156.50	D014769	1.50	<0.005		0.001	
	156.50	158.00	D014770	1.50	2.560		2.560	
	158.00	159.50	D014771	1.50	0.088		0.088	
	159.50	161.00	D014772	1.50	<0.005		0.001	
	161.00	162.50	D014773	1.50	0.111		0.111	
	162.50	164.00	D014774	1.50	0.016		0.016	
	164.00	165.50	D014776	1.50	<0.005		0.001	
	165.50	167.00	D014777	1.50	0.241		0.241	
	167.00	168.00	D014778	1.00	0.610		0.610	
	168.00	169.50	D014779	1.50	0.022		0.022	
	169.50	171.00	D014780	1.50	0.033		0.033	
	171.00	172.50	D014781	1.50	<0.005		0.001	
	172.50	174.00	D014782	1.50	<0.005		0.001	
	174.00	175.50	D014783	1.50	0.007		0.007	
	175.50	177.00	D014784	1.50	<0.005		0.001	
	177.00	178.50	D014786	1.50	0.063		0.063	
178.50	180.00	QZVN	178.50	180.00	D014787	1.50	0.026	0.026
		<b>Veine de Quartz massive 35°</b>	180.00	181.50	D014788	1.50	0.075	0.075
		Veine de qtz blanc.	181.50	183.00	D014789	1.50	0.009	0.009
			183.00	184.50	D014790	1.50	0.008	0.008
			184.50	186.00	D014791	1.50	0.007	0.007
			186.00	187.50	D014792	1.50	0.153	0.153
			187.50	189.00	D014793	1.50	0.014	0.014
			189.00	190.50	D014794	1.50	<0.005	0.001
			190.50	192.00	D014796	1.50	<0.005	0.001
			192.00	193.50	D014797	1.50	0.006	0.006
			193.50	195.00	D014798	1.50	0.014	0.014
			195.00	196.50	D014799	1.50	0.006	0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	196.50	198.00	D014801	1.50	0.024		0.024
	198.00	199.50	D014802	1.50	0.046		0.046
	199.50	201.00	D014803	1.50	0.008		0.008
	201.00	202.50	D014804	1.50	0.009		0.009
	202.50	204.00	D014806	1.50	0.012		0.012
	204.00	205.50	D014807	1.50	0.025		0.025
	205.50	207.00	D014808	1.50	0.007		0.007
	207.00	208.50	D014809	1.50	0.005		0.005
	208.50	210.00	D014810	1.50	0.009		0.009
	210.00	211.50	D014811	1.50	<0.005		0.001
	211.50	213.00	D014812	1.50	0.010		0.010
	213.00	214.50	D014813	1.50	<0.005		0.001
	214.50	216.00	D014814	1.50	0.010		0.010
	216.00	217.50	D014816	1.50	0.006		0.006
	217.50	219.00	D014817	1.50	<0.005		0.001
	219.00	220.50	D014818	1.50	<0.005		0.001
	220.50	222.00	D014819	1.50	<0.005		0.001
	222.00	223.50	D014820	1.50	<0.005		0.001
	223.50	225.00	D014821	1.50	0.005		0.005
	225.00	226.50	D014822	1.50	<0.005		0.001
	226.50	228.00	D014823	1.50	<0.005		0.001
	228.00	229.50	D014824	1.50	<0.005		0.001
	229.50	231.00	D014826	1.50	0.005		0.005
	231.00	232.50	D014827	1.50	0.014		0.014
	232.50	234.00	D014828	1.50	0.010		0.010
	234.00	235.50	D014829	1.50	0.006		0.006
	235.50	237.00	D014830	1.50	<0.005		0.001
	237.00	238.50	D014831	1.50	<0.005		0.001
	238.50	240.00	D014832	1.50	<0.005		0.001
	240.00	241.50	D014833	1.50	<0.005		0.001
	241.50	243.00	D014834	1.50	0.007		0.007
	243.00	244.50	D014836	1.50	0.056		0.056
	244.50	246.00	D014837	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.00	247.50	D014838	1.50	0.075		0.075
	247.50	249.00	D014839	1.50	0.056		0.056
	249.00	250.50	D014841	1.50	0.012		0.012
	250.50	252.00	D014842	1.50	0.005		0.005
	252.00	253.50	D014843	1.50	<0.005		0.001
	253.50	255.00	D014844	1.50	<0.005		0.001
	255.00	256.50	D014846	1.50	0.012		0.012
	256.50	258.00	D014847	1.50	0.012		0.012
	258.00	259.50	D014848	1.50	0.007		0.007
	259.50	261.00	D014849	1.50	<0.005		0.001
	261.00	262.50	D014850	1.50	<0.005		0.001
	262.50	264.00	D014851	1.50	<0.005		0.001
	264.00	265.50	D014852	1.50	<0.005		0.001
	265.50	267.00	D014853	1.50	<0.005		0.001
	267.00	268.50	D014854	1.50	0.005		0.005
	268.50	270.00	D014856	1.50	<0.005		0.001
	270.00	271.50	D014857	1.50	<0.005		0.001
	271.50	273.00	D014858	1.50	<0.005		0.001
	273.00	274.50	D014859	1.50	<0.005		0.001
	274.50	276.00	D014860	1.50	<0.005		0.001
	276.00	277.50	D014861	1.50	<0.005		0.001
	277.50	279.00	D014862	1.50	<0.005		0.001
	279.00	280.50	D014863	1.50	<0.005		0.001
	280.50	282.00	D014864	1.50	<0.005		0.001
	282.00	283.50	D014866	1.50	<0.005		0.001
	283.50	285.00	D014867	1.50	<0.005		0.001
	285.00	286.50	D014868	1.50	0.006		0.006
	286.50	288.00	D014869	1.50	<0.005		0.001
	288.00	289.50	D014870	1.50	<0.005		0.001
	289.50	291.00	D014871	1.50	<0.005		0.001
	291.00	292.50	D014872	1.50	<0.005		0.001
	292.50	294.00	D014873	1.50	<0.005		0.001
	294.00	295.50	D014874	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	295.50	297.00	D014876	1.50	<0.005		0.001
	297.00	298.50	D014877	1.50	<0.005		0.001
	298.50	300.00	D014878	1.50	<0.005		0.001
	300.00	301.50	D014879	1.50	<0.005		0.001
	301.50	303.00	D014881	1.50	<0.005		0.001
	303.00	304.50	D014882	1.50	<0.005		0.001
	304.50	306.00	D014883	1.50	<0.005		0.001
	306.00	307.50	D014884	1.50	<0.005		0.001
	307.50	309.00	D014886	1.50	<0.005		0.001
	309.00	310.50	D014887	1.50	<0.005		0.001
	310.50	312.00	D014888	1.50	<0.005		0.001
	312.00	313.50	D014889	1.50	<0.005		0.001
	313.50	315.00	D014890	1.50	<0.005		0.001
	315.00	316.50	D014891	1.50	<0.005		0.001
	316.50	318.00	D014892	1.50	<0.005		0.001
	318.00	319.50	D014893	1.50	<0.005		0.001
	319.50	321.00	D014894	1.50	<0.005		0.001
	321.00	322.50	D014896	1.50	<0.005		0.001
	322.50	324.00	D014897	1.50	<0.005		0.001
	324.00	325.50	D014898	1.50	<0.005		0.001
	325.50	327.00	D014899	1.50	<0.005		0.001
	327.00	328.50	D014900	1.50	<0.005		0.001
	328.50	330.00	D014901	1.50	<0.005		0.001
	330.00	331.50	D014902	1.50	<0.005		0.001
	331.50	333.00	D014903	1.50	<0.005		0.001
	333.00	334.50	D014904	1.50	<0.005		0.001
	334.50	336.00	D014906	1.50	<0.005		0.001
	336.00	337.50	D014907	1.50	<0.005		0.001
	337.50	339.00	D014908	1.50	<0.005		0.001
	339.00	340.50	D014909	1.50	<0.005		0.001
	340.50	342.00	D014910	1.50	<0.005		0.001
	342.00	343.50	D014911	1.50	<0.005		0.001
	343.50	345.00	D014912	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.00	346.50	D014913	1.50	<0.005		0.001
	346.50	348.00	D014914	1.50	0.009		0.009
	348.00	349.50	D014916	1.50	<0.005		0.001
	349.50	351.00	D014917	1.50	<0.005		0.001
	351.00	352.50	D014918	1.50	<0.005		0.001
	352.50	354.00	D014919	1.50	<0.005		0.001
	354.00	355.50	D014921	1.50	<0.005		0.001
	355.50	357.00	D014922	1.50	<0.005		0.001
	357.00	358.50	D014923	1.50	<0.005		0.001
	358.50	360.00	D014924	1.50	<0.005		0.001
	360.00	361.50	D014926	1.50	<0.005		0.001
	361.50	363.00	D014927	1.50	<0.005		0.001
	363.00	364.50	D014928	1.50	<0.005		0.001
	364.50	366.00	D014929	1.50	<0.005		0.001
	366.00	367.50	D014930	1.50	<0.005		0.001
	367.50	369.00	D014931	1.50	0.008		0.008
	369.00	370.50	D014932	1.50	<0.005		0.001
	370.50	372.00	D014933	1.50	<0.005		0.001
	372.00	373.50	D014934	1.50	<0.005		0.001
	373.50	375.00	D014936	1.50	0.010		0.010
	375.00	376.50	D014937	1.50	0.005		0.005
	376.50	378.00	D014938	1.50	<0.005		0.001
	378.00	379.50	D014939	1.50	<0.005		0.001
	379.50	381.00	D014940	1.50	0.005		0.005
	381.00	382.50	D014941	1.50	0.005		0.005
	382.50	384.00	D014942	1.50	0.005		0.005
	384.00	385.50	D014943	1.50	<0.005		0.001
	385.50	387.00	D014944	1.50	0.005		0.005
	387.00	388.50	D014946	1.50	<0.005		0.001
	388.50	390.00	D014947	1.50	0.011		0.011
	390.00	391.50	D014948	1.50	<0.005		0.001
	391.50	393.00	D014949	1.50	<0.005		0.001
	393.00	394.50	D014950	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	394.50	396.00	D014951	1.50	<0.005		0.001
	396.00	397.50	D014952	1.50	<0.005		0.001
	397.50	399.00	D014953	1.50	<0.005		0.001
	399.00	400.50	D014954	1.50	0.007		0.007
	400.50	402.00	D014956	1.50	0.012		0.012
	402.00	403.50	D014957	1.50	0.008		0.008
	403.50	405.00	D014958	1.50	<0.005		0.001
	405.00	406.50	D014959	1.50	0.009		0.009
	406.50	408.00	D014961	1.50	<0.005		0.001
	408.00	409.50	D014962	1.50	<0.005		0.001
	409.50	411.00	D014963	1.50	<0.005		0.001
	411.00	412.50	D014964	1.50	<0.005		0.001
	412.50	414.00	D014966	1.50	<0.005		0.001
	414.00	415.50	D014967	1.50	<0.005		0.001
	415.50	417.00	D014968	1.50	0.018		0.018
	417.00	418.50	D014969	1.50	0.005		0.005
	418.50	420.00	D014970	1.50	0.218		0.218
	420.00	421.50	D014971	1.50	0.032		0.032
	421.50	423.00	D014972	1.50	0.021		0.021
	423.00	424.00	D014973	1.00	0.028		0.028
	424.00	425.50	D014974	1.50	0.296		0.296
	425.50	427.00	D014976	1.50	3.030		3.030
	427.00	428.50	D014977	1.50	7.030		7.030
	428.50	430.00	D014978	1.50	5.700		5.700
	430.00	431.50	D014979	1.50	2.730		2.730
	431.50	433.00	D014980	1.50	2.310		2.310
	433.00	434.50	D014981	1.50	0.862		0.862
	434.50	436.00	D014982	1.50	0.838		0.838
	436.00	437.50	D014983	1.50	1.585		1.585
	437.50	439.00	D014984	1.50	0.300		0.300
	439.00	440.50	D014986	1.50	0.423		0.423
	440.50	442.00	D014987	1.50	1.885		1.885
	442.00	443.50	D014988	1.50	0.860		0.860

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	443.50	445.00	D014989	1.50	0.024		0.024
	445.00	446.50	D014990	1.50	0.021		0.021
	446.50	448.00	D014991	1.50	0.005		0.005
	448.00	449.00	D014992	1.00	<0.005		0.001
	449.00	450.00	D014993	1.00	0.021		0.021
450.00	Fin du sondage Nombre d'échantillons : 301 Nombre d'échantillons QAQC : 41 Longueur totale échantillonnée : 449.00						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.00	4.00	D014655	L	0.00	2.110	2.110
17.50	19.00	D014665	D014664	1.50	0.079	0.079
31.00	31.00	D014675	M	0.00	3.070	3.070
37.00	37.00	D014680	M1	0.00	<0.005	0.001
43.00	44.50	D014685	D014684	1.50	<0.005	0.001
56.50	56.50	D014695	J	0.00	0.772	0.772
70.00	71.50	D014705	D014704	1.50	<0.005	0.001
83.20	83.20	D014715	K	0.00	1.065	1.065
89.00	89.00	D014720	M1	0.00	<0.005	0.001
95.00	96.50	D014725	D014724	1.50	0.852	0.852
108.50	108.50	D014735	J	0.00	0.758	0.758
122.00	123.50	D014745	D014744	1.50	0.029	0.029
135.50	135.50	D014755	K	0.00	1.110	1.110
149.00	150.50	D014765	D014764	1.50	0.277	0.277
162.50	162.50	D014775	L	0.00	2.110	2.110
175.50	177.00	D014785	D014784	1.50	<0.005	0.001
189.00	189.00	D014795	M	0.00	3.180	3.180
195.00	195.00	D014800	M1	0.00	<0.005	0.001
201.00	202.50	D014805	D014804	1.50	0.010	0.010
214.50	214.50	D014815	J	0.00	0.761	0.761
228.00	229.50	D014825	D014824	1.50	0.005	0.005
241.50	241.50	D014835	K	0.00	1.020	1.020
247.50	247.50	D014840	M1	0.00	<0.005	0.001
253.50	255.00	D014845	D014844	1.50	<0.005	0.001
267.00	267.00	D014855	J	0.00	0.740	0.740
280.50	282.00	D014865	D014864	1.50	<0.005	0.001
294.00	294.00	D014875	K	0.00	1.195	1.195
300.00	300.00	D014880	M1	0.00	<0.005	0.001
306.00	307.50	D014885	D014884	1.50	<0.005	0.001
319.50	319.50	D014895	L	0.00	2.100	2.100
333.00	334.50	D014905	D014904	1.50	0.027	0.027
346.50	346.50	D014915	M	0.00	2.950	2.950
352.50	352.50	D014920	M1	0.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
358.50	360.00	D014925	D014924	1.50	<0.005	0.001
372.00	372.00	D014935	L	0.00	2.130	2.130
385.50	387.00	D014945	D014944	1.50	0.005	0.005
399.00	399.00	D014955	L	0.00	2.140	2.140
405.00	405.00	D014960	M1	0.00	<0.005	0.001
411.00	412.50	D014965	D014964	1.50	<0.005	0.001
424.00	424.00	D014975	J	0.00	0.786	0.786
437.50	439.00	D014985	D014984	1.50	0.292	0.292

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-178**

Titre minier :

Section :                      630300

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    David RUHARA

Lot :

Du :                              2010-05-04

Date de description :

Au :                              2010-05-13

Collet

UTM

Azimut :                        3.00°

Est                              630 296.1

Plongée :                       -71.00°

Nord                            5 374 221.8

Longueur :                    426.00 m

Élévation                      308.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	0.70°	-71.40°	Oui
Reflex	9.00	1.60°	-71.40°	Non
Reflex	12.00	1.90°	-71.40°	Non
Reflex	15.00	2.20°	-71.40°	Non
Reflex	18.00	2.50°	-71.40°	Non
Reflex	21.00	1.80°	-71.40°	Non
Reflex	24.00	1.60°	-71.40°	Non
Reflex	27.00	1.90°	-71.40°	Non
Reflex	30.00	2.00°	-71.30°	Non
Reflex	33.00	0.50°	-71.30°	Oui
Reflex	36.00	1.20°	-71.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	1.60°	-71.30°	Non
Reflex	42.00	1.70°	-71.30°	Non
Reflex	45.00	2.00°	-71.30°	Non
Reflex	48.00	1.60°	-71.30°	Non
Reflex	51.00	1.70°	-71.30°	Non
Reflex	54.00	2.20°	-71.40°	Non
Reflex	57.00	2.70°	-71.40°	Non
Reflex	60.00	2.50°	-71.40°	Non
Reflex	63.00	2.30°	-71.40°	Non
Reflex	66.00	2.30°	-71.40°	Non
Reflex	69.00	3.00°	-71.40°	Non
Reflex	72.00	3.50°	-71.40°	Oui

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	2.20°	-71.40°	Non
Reflex	78.00	2.60°	-71.30°	Non
Reflex	81.00	3.60°	-71.40°	Non
Reflex	84.00	3.00°	-71.40°	Non
Reflex	87.00	3.40°	-71.40°	Non
Reflex	90.00	1.90°	-71.30°	Non
Reflex	93.00	1.40°	-71.40°	Non
Reflex	96.00	0.40°	-71.30°	Non
Reflex	99.00	1.20°	-71.30°	Non
Reflex	102.00	2.00°	-71.30°	Non
Reflex	105.00	1.20°	-71.30°	Non
Reflex	108.00	2.30°	-71.30°	Non
Reflex	111.00	3.40°	-71.30°	Oui
Reflex	114.00	2.90°	-71.30°	Non
Reflex	117.00	3.30°	-71.30°	Non
Reflex	120.00	2.50°	-71.30°	Non
Reflex	123.00	1.60°	-71.20°	Non
Reflex	126.00	0.10°	-71.20°	Non
Reflex	129.00	2.30°	-71.20°	Non
Reflex	132.00	1.30°	-71.20°	Non
Reflex	135.00	2.80°	-71.20°	Non
Reflex	138.00	2.30°	-71.20°	Non
Reflex	141.00	2.60°	-71.20°	Non
Reflex	144.00	2.00°	-71.20°	Non
Reflex	147.00	2.80°	-71.20°	Non
Reflex	150.00	2.60°	-71.20°	Non
Reflex	153.00	3.20°	-71.20°	Non
Reflex	156.00	3.10°	-71.20°	Non
Reflex	159.00	3.30°	-71.20°	Non
Reflex	162.00	3.70°	-71.20°	Non
Reflex	165.00	2.60°	-71.10°	Non
Reflex	168.00	3.50°	-71.20°	Non
Reflex	171.00	2.60°	-71.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	174.00	3.30°	-71.10°	Non
Reflex	177.00	3.20°	-71.10°	Non
Reflex	180.00	1.80°	-71.10°	Non
Reflex	183.00	3.60°	-71.10°	Non
Reflex	186.00	1.60°	-71.10°	Non
Reflex	189.00	2.40°	-71.10°	Non
Reflex	192.00	1.60°	-71.10°	Non
Reflex	195.00	0.20°	-71.10°	Non
Reflex	198.00	359.80°	-71.10°	Non
Reflex	201.00	0.40°	-71.00°	Non
Reflex	204.00	359.80°	-71.00°	Non
Reflex	207.00	0.90°	-71.10°	Non
Reflex	210.00	359.80°	-71.00°	Non
Reflex	213.00	0.50°	-71.10°	Non
Reflex	216.00	4.00°	-71.00°	Non
Reflex	219.00	4.00°	-71.20°	Non
Reflex	222.00	3.40°	-71.10°	Non
Reflex	225.00	4.20°	-71.10°	Non
Reflex	228.00	0.20°	-71.10°	Oui
Reflex	231.00	359.60°	-71.10°	Oui
Reflex	234.00	3.60°	-71.00°	Non
Reflex	237.00	4.20°	-71.10°	Non
Reflex	240.00	0.60°	-71.10°	Oui
Reflex	243.00	3.10°	-71.00°	Non
Reflex	246.00	4.30°	-71.00°	Non
Reflex	249.00	5.00°	-71.00°	Non
Reflex	252.00	4.80°	-71.00°	Non
Reflex	255.00	5.30°	-71.00°	Non
Reflex	258.00	4.90°	-71.00°	Non
Reflex	261.00	6.30°	-71.00°	Oui
Reflex	264.00	4.70°	-71.10°	Non
Reflex	267.00	2.60°	-71.10°	Oui
Reflex	270.00	3.40°	-71.10°	Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	4.20°	-71.10°	Non	Reflex	372.00	8.90°	-70.60°	Non
Reflex	276.00	4.00°	-71.10°	Non	Reflex	375.00	9.40°	-70.60°	Non
Reflex	279.00	3.40°	-71.10°	Oui	Reflex	378.00	9.30°	-70.60°	Non
Reflex	282.00	4.10°	-71.10°	Non	Reflex	381.00	9.50°	-70.60°	Non
Reflex	285.00	4.10°	-71.10°	Non	Reflex	384.00	10.30°	-70.60°	Non
Reflex	288.00	0.40°	-71.00°	Oui	Reflex	387.00	9.90°	-70.50°	Non
Reflex	291.00	4.30°	-71.00°	Non	Reflex	390.00	5.70°	-70.40°	Oui
Reflex	294.00	3.30°	-71.00°	Oui	Reflex	393.00	10.30°	-70.50°	Non
Reflex	297.00	5.30°	-71.00°	Non	Reflex	396.00	10.40°	-70.40°	Non
Reflex	300.00	5.00°	-71.00°	Non	Reflex	399.00	9.80°	-70.30°	Non
Reflex	303.00	5.60°	-71.00°	Non	Reflex	402.00	10.10°	-70.30°	Non
Reflex	306.00	4.50°	-71.00°	Oui	Reflex	405.00	10.80°	-70.20°	Non
Reflex	309.00	5.90°	-71.00°	Non	Reflex	408.00	11.00°	-70.20°	Non
Reflex	312.00	5.80°	-71.00°	Non	Reflex	411.00	10.80°	-70.20°	Non
Reflex	315.00	5.40°	-71.10°	Non	Reflex	414.00	10.00°	-70.20°	Non
Reflex	318.00	5.60°	-71.10°	Non	Reflex	417.00	11.40°	-70.10°	Non
Reflex	321.00	6.10°	-71.10°	Non	Reflex	420.00	11.60°	-70.20°	Non
Reflex	324.00	6.20°	-71.00°	Non	Reflex	423.00	10.70°	-70.10°	Non
Reflex	327.00	6.40°	-71.00°	Non	Reflex	426.00	11.20°	-70.10°	Non
Reflex	330.00	6.50°	-71.00°	Non					
Reflex	333.00	6.40°	-71.00°	Non					
Reflex	336.00	7.20°	-71.00°	Non					
Reflex	339.00	7.10°	-71.00°	Non					
Reflex	342.00	6.50°	-71.00°	Non					
Reflex	345.00	6.90°	-71.00°	Non					
Reflex	348.00	5.70°	-71.00°	Oui					
Reflex	351.00	6.70°	-70.90°	Non					
Reflex	354.00	7.50°	-70.90°	Non					
Reflex	357.00	7.70°	-70.80°	Non					
Reflex	360.00	8.40°	-70.80°	Non					
Reflex	363.00	9.10°	-70.80°	Non					
Reflex	366.00	8.50°	-70.70°	Non					
Reflex	369.00	8.30°	-70.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.90	MT						
		<b>Mort-terrain</b>						
0.90	426.00	SY; FIN; POR	0.90	2.00	D017005	1.10	0.009	0.009
		<b>Syénite; Grains fins; Porphyrique</b>	2.00	3.50	D017006	1.50	0.006	0.006
		Syénite, à grains fins, porphyrique avec de phénocristaux Xmm	3.50	5.00	D017008	1.50	0.014	0.014
		repartis différentiellement.	5.00	6.50	D017009	1.50	<0.005	0.001
			6.50	8.00	D017010	1.50	0.011	0.011
			8.00	9.50	D017011	1.50	0.046	0.046
			9.50	11.00	D017012	1.50	0.053	0.053
			11.00	12.50	D017013	1.50	<0.005	0.001
			12.50	14.00	D017014	1.50	0.102	0.102
			14.00	15.50	D017015	1.50	0.064	0.064
			15.50	17.00	D017016	1.50	0.082	0.082
			17.00	18.50	D017018	1.50	0.173	0.173
			18.50	20.00	D017019	1.50	0.070	0.070
			20.00	21.50	D017020	1.50	0.123	0.123
			21.50	23.00	D017021	1.50	0.247	0.247
			23.00	24.50	D017022	1.50	0.087	0.087
			24.50	26.00	D017023	1.50	0.192	0.192
			26.00	27.50	D017024	1.50	0.222	0.222
			27.50	29.00	D017025	1.50	0.113	0.113
			29.00	30.50	D017026	1.50	0.013	0.013
			30.50	32.00	D017028	1.50	0.016	0.016
			32.00	33.50	D017029	1.50	0.143	0.143
			33.50	35.00	D017030	1.50	0.072	0.072
			35.00	36.50	D017031	1.50	0.032	0.032
			36.50	38.00	D017032	1.50	0.009	0.009
			38.00	39.50	D017033	1.50	0.079	0.079
			39.50	41.00	D017034	1.50	0.051	0.051
			41.00	42.50	D017035	1.50	0.035	0.035
			42.50	44.00	D017036	1.50	0.022	0.022
			44.00	45.50	D017038	1.50	<0.005	0.001
			45.50	47.00	D017039	1.50	<0.005	0.001
			47.00	48.50	D017040	1.50	0.080	0.080

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.50	50.00	D017041	1.50	0.053		0.053
	50.00	51.50	D017043	1.50	<0.005		0.001
	51.50	53.00	D017044	1.50	0.005		0.005
	53.00	54.50	D017045	1.50	0.010		0.010
	54.50	56.00	D017046	1.50	0.011		0.011
	56.00	57.50	D017048	1.50	0.028		0.028
	57.50	59.00	D017049	1.50	<0.005		0.001
	59.00	60.50	D017050	1.50	0.010		0.010
	60.50	62.00	D017051	1.50	0.023		0.023
	62.00	63.50	D017052	1.50	0.050		0.050
	63.50	65.00	D017053	1.50	0.096		0.096
	65.00	66.50	D017054	1.50	0.085		0.085
	66.50	68.00	D017055	1.50	0.021		0.021
	68.00	69.50	D017056	1.50	0.180		0.180
	69.50	71.00	D017058	1.50	0.035		0.035
	71.00	72.50	D017059	1.50	<0.005		0.001
	72.50	74.00	D017060	1.50	0.077		0.077
	74.00	75.50	D017061	1.50	0.084		0.084
	75.50	77.00	D017062	1.50	0.057		0.057
	77.00	78.50	D017063	1.50	0.014		0.014
	78.50	80.00	D017064	1.50	0.133		0.133
	80.00	81.50	D017065	1.50	0.009		0.009
	81.50	83.00	D017066	1.50	0.015		0.015
	83.00	84.50	D017068	1.50	0.200		0.200
	84.50	86.00	D017069	1.50	0.092		0.092
	86.00	87.50	D017070	1.50	0.891		0.891
	87.50	89.00	D017071	1.50	0.006		0.006
	89.00	90.50	D017072	1.50	0.464		0.464
	90.50	92.00	D017073	1.50	0.271		0.271
	92.00	93.50	D017074	1.50	1.470		1.470
	93.50	95.00	D017075	1.50	0.948		0.948
	95.00	96.50	D017076	1.50	3.810		3.810
	96.50	98.00	D017078	1.50	3.830		3.830

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.00	99.50	D017079	1.50	3.750		3.750
	99.50	101.00	D017080	1.50	1.605		1.605
	101.00	102.50	D017081	1.50	1.195		1.195
	102.50	104.00	D017083	1.50	1.525		1.525
	104.00	105.50	D017084	1.50	2.040		2.040
	105.50	107.00	D017085	1.50	0.146		0.146
	107.00	108.50	D017086	1.50	0.410		0.410
	108.50	110.00	D017088	1.50	0.037		0.037
	110.00	111.50	D017089	1.50	0.183		0.183
	111.50	113.00	D017090	1.50	0.382		0.382
	113.00	114.50	D017091	1.50	0.023		0.023
	114.50	116.00	D017092	1.50	0.006		0.006
	116.00	117.50	D017093	1.50	0.271		0.271
	117.50	119.00	D017094	1.50	0.020		0.020
	119.00	120.50	D017095	1.50	<0.005		0.001
	120.50	122.00	D017096	1.50	<0.005		0.001
	122.00	123.50	D017098	1.50	0.006		0.006
	123.50	125.00	D017099	1.50	0.090		0.090
	125.00	126.50	D017100	1.50	0.033		0.033
	126.50	128.00	D017101	1.50	0.047		0.047
	128.00	129.50	D017102	1.50	0.066		0.066
	129.50	131.00	D017103	1.50	1.705		1.705
	131.00	132.50	D017104	1.50	2.770		2.770
	132.50	134.00	D017105	1.50	0.012		0.012
	134.00	135.50	D017106	1.50	0.008		0.008
	135.50	137.00	D017108	1.50	0.018		0.018
	137.00	138.50	D017109	1.50	0.029		0.029
	138.50	140.00	D017110	1.50	0.008		0.008
	140.00	141.50	D017111	1.50	0.009		0.009
	141.50	143.00	D017112	1.50	0.020		0.020
	143.00	144.50	D017113	1.50	0.006		0.006
	144.50	146.00	D017114	1.50	0.005		0.005
	146.00	147.50	D017115	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	147.50	149.00	D017116	1.50	0.005		0.005	
	149.00	150.50	D017118	1.50	<0.005		0.001	
	150.50	152.00	D017119	1.50	0.011		0.011	
	152.00	153.50	D017120	1.50	0.005		0.005	
	153.50	155.00	D017121	1.50	<0.005		0.001	
	155.00	156.50	D017123	1.50	<0.005		0.001	
	156.50	158.00	D017124	1.50	<0.005		0.001	
	158.00	159.50	D017125	1.50	0.060		0.060	
	159.50	161.00	D017126	1.50	0.077		0.077	
	161.00	162.50	D017128	1.50	0.042		0.042	
	162.50	164.00	D017129	1.50	0.021		0.021	
	164.00	165.50	D017130	1.50	<0.005		0.001	
	165.50	167.00	D017131	1.50	0.024		0.024	
	167.00	168.50	D017132	1.50	0.084		0.084	
	168.50	170.00	D017133	1.50	0.096		0.096	
	170.00	171.50	D017134	1.50	<0.005		0.001	
	171.50	173.00	D017135	1.50	<0.005		0.001	
	173.00	174.50	D017136	1.50	<0.005		0.001	
	174.50	176.00	D017138	1.50	0.026		0.026	
	176.00	177.50	D017139	1.50	0.017		0.017	
	177.50	179.00	D017140	1.50	0.019		0.019	
	179.00	180.50	D017141	1.50	0.024		0.024	
	180.50	182.00	D017142	1.50	0.017		0.017	
	182.00	183.50	D017143	1.50	1.160		1.160	
	183.50	185.00	D017144	1.50	0.209		0.209	
	185.00	186.50	D017145	1.50	0.131		0.131	
	186.50	188.00	D017146	1.50	0.070		0.070	
	188.00	189.50	D017148	1.50	0.263		0.263	
	189.50	191.00	D017149	1.50	0.661		0.661	
	191.00	192.50	D017150	1.50	1.330		1.330	
192.00	200.00	FRC	192.50	194.00	D017151	1.50	0.079	0.079
		<b>Fracturé</b>	194.00	195.50	D017152	1.50	0.013	0.013
		Zone fracturée.	195.50	197.00	D017153	1.50	0.041	0.041

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.00	198.50	D017154	1.50	0.015		0.015
	198.50	200.00	D017155	1.50	0.038		0.038
	200.00	201.50	D017156	1.50	0.027		0.027
	201.50	203.00	D017158	1.50	0.008		0.008
	203.00	204.50	D017159	1.50	<0.005		0.001
	204.50	206.00	D017160	1.50	<0.005		0.001
	206.00	207.50	D017161	1.50	0.034		0.034
	207.50	209.00	D017163	1.50	<0.005		0.001
	209.00	210.50	D017164	1.50	<0.005		0.001
	210.50	212.00	D017165	1.50	<0.005		0.001
	212.00	213.50	D017166	1.50	0.009		0.009
	213.50	215.00	D017168	1.50	<0.005		0.001
	215.00	216.50	D017169	1.50	0.007		0.007
	216.50	218.00	D017170	1.50	<0.005		0.001
	218.00	219.50	D017171	1.50	<0.005		0.001
	219.50	221.00	D017172	1.50	<0.005		0.001
	221.00	222.50	D017173	1.50	<0.005		0.001
	222.50	224.00	D017174	1.50	0.008		0.008
	224.00	225.50	D017175	1.50	<0.005		0.001
	225.50	227.00	D017176	1.50	0.031		0.031
	227.00	228.50	D017178	1.50	0.009		0.009
	228.50	230.00	D017179	1.50	<0.005		0.001
	230.00	231.50	D017180	1.50	0.006		0.006
	231.50	233.00	D017181	1.50	<0.005		0.001
	233.00	234.50	D017182	1.50	<0.005		0.001
	234.50	236.00	D017183	1.50	0.006		0.006
	236.00	237.50	D017184	1.50	<0.005		0.001
	237.50	239.00	D017185	1.50	<0.005		0.001
	239.00	240.50	D017186	1.50	<0.005		0.001
	240.50	242.00	D017188	1.50	0.005		0.005
	242.00	243.50	D017189	1.50	0.010		0.010
	243.50	245.00	D017190	1.50	<0.005		0.001
	245.00	246.50	D017191	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.50	248.00	D017192	1.50	<0.005		0.001
	248.00	249.50	D017193	1.50	<0.005		0.001
	249.50	251.00	D017194	1.50	<0.005		0.001
	251.00	252.50	D017195	1.50	<0.005		0.001
	252.50	254.00	D017196	1.50	<0.005		0.001
	254.00	255.50	D017198	1.50	<0.005		0.001
	255.50	257.00	D017199	1.50	<0.005		0.001
	257.00	258.50	D017200	1.50	<0.005		0.001
	258.50	260.00	D017201	1.50	<0.005		0.001
	260.00	261.50	D017203	1.50	<0.005		0.001
	261.50	263.00	D017204	1.50	<0.005		0.001
	263.00	264.50	D017205	1.50	<0.005		0.001
	264.50	266.00	D017206	1.50	0.006		0.006
	266.00	267.50	D017208	1.50	<0.005		0.001
	267.50	269.00	D017209	1.50	<0.005		0.001
	269.00	270.50	D017210	1.50	<0.005		0.001
	270.50	272.00	D017211	1.50	0.006		0.006
	272.00	273.50	D017212	1.50	0.005		0.005
	273.50	275.00	D017213	1.50	0.005		0.005
	275.00	276.50	D017214	1.50	0.012		0.012
	276.50	278.00	D017215	1.50	0.006		0.006
	278.00	279.50	D017216	1.50	0.030		0.030
	279.50	281.00	D017218	1.50	<0.005		0.001
	281.00	282.50	D017219	1.50	0.005		0.005
	282.50	284.00	D017220	1.50	0.005		0.005
	284.00	285.50	D017221	1.50	<0.005		0.001
	285.50	287.00	D017222	1.50	<0.005		0.001
	287.00	288.50	D017223	1.50	0.005		0.005
	288.50	290.00	D017224	1.50	0.034		0.034
	290.00	291.50	D017225	1.50	0.029		0.029
	291.50	293.00	D017226	1.50	0.031		0.031
	293.00	294.50	D017228	1.50	0.008		0.008
	294.50	296.00	D017229	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.00	297.50	D017230	1.50	<0.005		0.001
	297.50	299.00	D017231	1.50	<0.005		0.001
	299.00	300.50	D017232	1.50	0.020		0.020
	300.50	302.00	D017233	1.50	0.035		0.035
	302.00	303.50	D017234	1.50	<0.005		0.001
	303.50	305.00	D017235	1.50	0.026		0.026
	305.00	306.50	D017236	1.50	0.006		0.006
	306.50	308.00	D017238	1.50	<0.005		0.001
	308.00	309.50	D017239	1.50	<0.005		0.001
	309.50	311.00	D017240	1.50	<0.005		0.001
	311.00	312.50	D017241	1.50	0.006		0.006
	312.50	314.00	D017243	1.50	0.008		0.008
	314.00	315.50	D017244	1.50	<0.005		0.001
	315.50	317.00	D017245	1.50	<0.005		0.001
	317.00	318.50	D017246	1.50	0.016		0.016
	318.50	320.00	D017248	1.50	0.005		0.005
	320.00	321.50	D017249	1.50	<0.005		0.001
	321.50	323.00	D017250	1.50	<0.005		0.001
	323.00	324.50	D017251	1.50	<0.005		0.001
	324.50	326.00	D017252	1.50	<0.005		0.001
	326.00	327.50	D017253	1.50	<0.005		0.001
	327.50	329.00	D017254	1.50	<0.005		0.001
	329.00	330.50	D017255	1.50	<0.005		0.001
	330.50	332.00	D017256	1.50	<0.005		0.001
	332.00	333.50	D017258	1.50	0.006		0.006
	333.50	335.00	D017259	1.50	0.006		0.006
	335.00	336.50	D017260	1.50	0.005		0.005
	336.50	338.00	D017261	1.50	0.008		0.008
	338.00	339.50	D017262	1.50	0.020		0.020
	339.50	341.00	D017263	1.50	0.047		0.047
	341.00	342.50	D017264	1.50	0.005		0.005
	342.50	344.00	D017265	1.50	0.009		0.009
	344.00	345.50	D017266	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D017268	1.50	<0.005		0.001
	347.00	348.50	D017269	1.50	<0.005		0.001
	348.50	350.00	D017270	1.50	<0.005		0.001
	350.00	351.50	D017271	1.50	<0.005		0.001
	351.50	353.00	D017272	1.50	<0.005		0.001
	353.00	354.50	D017273	1.50	<0.005		0.001
	354.50	356.00	D017274	1.50	<0.005		0.001
	356.00	357.50	D017275	1.50	<0.005		0.001
	357.50	359.00	D017276	1.50	0.005		0.005
	359.00	360.50	D017278	1.50	<0.005		0.001
	360.50	362.00	D017279	1.50	<0.005		0.001
	362.00	363.50	D017280	1.50	<0.005		0.001
	363.50	365.00	D017281	1.50	0.006		0.006
	365.00	366.50	D017283	1.50	0.005		0.005
	366.50	368.00	D017284	1.50	0.006		0.006
	368.00	369.50	D017285	1.50	0.005		0.005
	369.50	371.00	D017286	1.50	<0.005		0.001
	371.00	372.50	D017288	1.50	0.007		0.007
	372.50	374.00	D017289	1.50	0.007		0.007
	374.00	375.50	D017290	1.50	0.022		0.022
	375.50	377.00	D017291	1.50	0.005		0.005
	377.00	378.50	D017292	1.50	0.006		0.006
	378.50	380.00	D017293	1.50	0.010		0.010
	380.00	381.50	D017294	1.50	0.007		0.007
	381.50	383.00	D017295	1.50	<0.005		0.001
	383.00	384.50	D017296	1.50	0.007		0.007
	384.50	386.00	D017298	1.50	<0.005		0.001
	386.00	387.50	D017299	1.50	0.006		0.006
	387.50	389.00	D017300	1.50	0.006		0.006
	389.00	390.50	D017301	1.50	0.008		0.008
	390.50	392.00	D017302	1.50	<0.005		0.001
	392.00	393.50	D017303	1.50	<0.005		0.001
	393.50	395.00	D017304	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	395.00	396.50	D017305	1.50	0.006		0.006
	396.50	398.00	D017306	1.50	0.007		0.007
	398.00	399.50	D017308	1.50	0.009		0.009
	399.50	401.00	D017309	1.50	0.009		0.009
	401.00	402.50	D017310	1.50	0.005		0.005
	402.50	404.00	D017311	1.50	0.005		0.005
	404.00	405.50	D017312	1.50	<0.005		0.001
	405.50	407.00	D017313	1.50	0.006		0.006
	407.00	408.50	D017314	1.50	0.005		0.005
	408.50	410.00	D017315	1.50	0.006		0.006
	410.00	411.50	D017316	1.50	0.005		0.005
	411.50	413.00	D017318	1.50	0.010		0.010
	413.00	414.50	D017319	1.50	0.005		0.005
	414.50	416.00	D017320	1.50	<0.005		0.001
	416.00	417.50	D017321	1.50	0.005		0.005
	417.50	419.00	D017323	1.50	0.006		0.006
	419.00	420.50	D017324	1.50	0.008		0.008
	420.50	422.00	D017325	1.50	<0.005		0.001
	422.00	423.50	D017326	1.50	<0.005		0.001
	423.50	425.00	D017328	1.50	<0.005		0.001
	425.00	426.00	D017329	1.00	<0.005		0.001
426.00	Fin du sondage Nombre d'échantillons : 284 Nombre d'échantillons QAQC : 41 Longueur totale échantillonnée : 425.10						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
2.00	3.50	D017007	A3	1.50	0.582	0.582
15.50	17.00	D017017	D017016	1.50	0.080	0.080
29.00	30.50	D017027	H	1.50	0.966	0.966
42.50	44.00	D017037	D017036	1.50	0.018	0.018
48.50	50.00	D017042	M1	1.50	0.101	0.101
54.50	56.00	D017047	D2	1.50	0.609	0.609
68.00	69.50	D017057	D017056	1.50	0.143	0.143
81.50	83.00	D017067	B4	1.50	2.640	2.640
95.00	96.50	D017077	D017076	1.50	4.310	4.310
101.00	102.50	D017082	M1	1.50	<0.005	0.001
107.00	108.50	D017087	M	1.50	3.170	3.170
120.50	122.00	D017097	D017096	1.50	<0.005	0.001
134.00	135.50	D017107	H	1.50	0.957	0.957
147.50	149.00	D017117	D017116	1.50	0.006	0.006
153.50	155.00	D017122	M1	1.50	<0.005	0.001
159.50	161.00	D017127	D2	1.50	0.804	0.804
173.00	174.50	D017137	D017136	1.50	0.005	0.005
186.50	188.00	D017147	A3	1.50	0.569	0.569
200.00	201.50	D017157	D017156	1.50	0.038	0.038
206.00	207.50	D017162	M1	1.50	<0.005	0.001
212.00	213.50	D017167	G2	1.50	3.770	3.770
225.50	227.00	D017177	D017176	1.50	0.023	0.023
239.00	240.50	D017187	C4	1.50	1.330	1.330
252.50	254.00	D017197	D017196	1.50	<0.005	0.001
258.50	260.00	D017202	M1	1.50	<0.005	0.001
264.50	266.00	D017207	D2	1.50	0.761	0.761
278.00	279.50	D017217	D017215	1.50	0.026	0.026
291.50	293.00	D017227	M	1.50	2.850	2.850
305.00	306.50	D017237	D017236	1.50	<0.005	0.001
311.00	312.50	D017242	M1	1.50	<0.005	0.001
317.00	318.50	D017247	G2	1.50	3.810	3.810
330.50	332.00	D017257	D017256	1.50	0.007	0.007
344.00	345.50	D017267	H	1.50	0.959	0.959

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
357.50	359.00	D017277	D017276	1.50	<0.005	0.001
363.50	365.00	D017282	M1	1.50	<0.005	0.001
369.50	371.00	D017287	A3	1.50	0.584	0.584
383.00	384.50	D017297	D017296	1.50	<0.005	0.001
396.50	398.00	D017307	B4	1.50	2.550	2.550
410.00	411.50	D017317	D017316	1.50	<0.005	0.001
416.00	417.50	D017322	M1	1.50	0.005	0.005
422.00	423.50	D017327	C4	1.50	1.310	1.310



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-179**

Titre minier :

Section :                      630300

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy Gbaguidi

Lot :

Du :                      2010-05-13

Date de description :

Au :                      2010-05-27

Collet

UTM

Azimut :                      3.00°  
 Plongée :                      -80.00°  
 Longueur :                      336.00 m

Est	630 296.1
Nord	5 374 221.7
Élévation	308.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	6.10°	-81.00°	Non
Reflex	9.00	6.40°	-81.10°	Non
Reflex	12.00	6.40°	-80.90°	Non
Reflex	15.00	6.40°	-80.90°	Non
Reflex	18.00	5.90°	-80.90°	Non
Reflex	21.00	3.90°	-80.90°	Oui
Reflex	24.00	3.70°	-80.90°	Oui
Reflex	27.00	5.30°	-80.80°	Non
Reflex	30.00	6.10°	-80.80°	Non
Reflex	33.00	4.10°	-80.80°	Non
Reflex	36.00	3.70°	-80.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	4.30°	-80.80°	Non
Reflex	42.00	3.70°	-80.90°	Non
Reflex	45.00	3.80°	-80.80°	Non
Reflex	48.00	4.50°	-80.80°	Non
Reflex	51.00	2.70°	-80.70°	Oui
Reflex	54.00	3.00°	-80.80°	Oui
Reflex	57.00	4.20°	-80.80°	Non
Reflex	60.00	4.50°	-80.80°	Non
Reflex	63.00	5.10°	-80.90°	Non
Reflex	66.00	4.50°	-80.90°	Non
Reflex	69.00	3.30°	-80.80°	Oui
Reflex	72.00	4.60°	-80.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	4.90°	-80.80°	Non
Reflex	78.00	4.40°	-80.70°	Non
Reflex	81.00	5.00°	-80.80°	Non
Reflex	84.00	5.70°	-80.80°	Non
Reflex	87.00	4.60°	-80.80°	Non
Reflex	90.00	5.70°	-80.70°	Non
Reflex	93.00	6.20°	-80.80°	Oui
Reflex	96.00	4.30°	-80.80°	Non
Reflex	99.00	4.00°	-80.90°	Non
Reflex	102.00	4.40°	-80.80°	Non
Reflex	105.00	3.80°	-80.70°	Non
Reflex	108.00	6.90°	-80.80°	Oui
Reflex	111.00	3.70°	-80.80°	Non
Reflex	114.00	3.50°	-80.80°	Non
Reflex	117.00	3.40°	-80.80°	Non
Reflex	120.00	2.90°	-80.80°	Non
Reflex	123.00	2.00°	-80.80°	Non
Reflex	126.00	3.10°	-80.80°	Non
Reflex	129.00	2.90°	-80.80°	Non
Reflex	132.00	3.70°	-80.80°	Non
Reflex	135.00	3.60°	-80.70°	Non
Reflex	138.00	2.40°	-80.80°	Non
Reflex	141.00	3.00°	-80.70°	Non
Reflex	144.00	3.60°	-80.70°	Non
Reflex	147.00	4.40°	-80.80°	Oui
Reflex	150.00	3.50°	-80.80°	Non
Reflex	153.00	4.00°	-80.70°	Non
Reflex	156.00	4.50°	-80.80°	Non
Reflex	159.00	3.90°	-80.80°	Non
Reflex	162.00	3.50°	-80.80°	Non
Reflex	165.00	4.10°	-80.70°	Non
Reflex	168.00	4.70°	-80.70°	Non
Reflex	171.00	5.40°	-80.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	174.00	5.40°	-80.80°	Non
Reflex	177.00	7.20°	-80.90°	Oui
Reflex	180.00	5.60°	-80.80°	Non
Reflex	183.00	6.40°	-80.80°	Non
Reflex	186.00	5.20°	-80.80°	Non
Reflex	189.00	5.50°	-80.90°	Non
Reflex	192.00	4.30°	-80.80°	Oui
Reflex	195.00	5.10°	-80.80°	Non
Reflex	198.00	4.20°	-80.80°	Non
Reflex	201.00	4.40°	-80.80°	Non
Reflex	204.00	5.20°	-81.00°	Non
Reflex	207.00	4.20°	-81.00°	Non
Reflex	210.00	5.00°	-81.10°	Non
Reflex	213.00	5.60°	-81.10°	Non
Reflex	216.00	4.80°	-81.00°	Non
Reflex	219.00	6.20°	-81.10°	Oui
Reflex	222.00	4.20°	-81.00°	Non
Reflex	225.00	4.60°	-81.00°	Non
Reflex	228.00	4.20°	-81.10°	Non
Reflex	231.00	4.30°	-81.10°	Non
Reflex	234.00	4.90°	-81.10°	Non
Reflex	237.00	4.80°	-81.10°	Non
Reflex	240.00	5.50°	-81.00°	Non
Reflex	243.00	3.60°	-81.00°	Non
Reflex	246.00	2.10°	-81.00°	Non
Reflex	249.00	3.70°	-81.00°	Non
Reflex	252.00	7.00°	-80.90°	Oui
Reflex	255.00	3.90°	-81.00°	Non
Reflex	258.00	4.30°	-81.10°	Non
Reflex	261.00	4.00°	-81.00°	Non
Reflex	264.00	4.40°	-81.00°	Non
Reflex	267.00	3.10°	-81.00°	Non
Reflex	270.00	3.10°	-81.00°	Non

Corporation Minière Osisko Div. Exploration

Déviaton

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	3.40°	-81.00°	Non					
Reflex	276.00	3.50°	-81.00°	Non					
Reflex	279.00	3.50°	-81.10°	Non					
Reflex	282.00	3.90°	-81.10°	Non					
Reflex	285.00	3.70°	-81.10°	Non					
Reflex	288.00	3.50°	-81.00°	Non					
Reflex	291.00	3.80°	-81.00°	Non					
Reflex	294.00	4.60°	-81.10°	Non					
Reflex	297.00	4.10°	-81.10°	Non					
Reflex	300.00	3.80°	-81.00°	Non					
Reflex	303.00	3.60°	-81.10°	Non					
Reflex	306.00	3.20°	-81.00°	Non					
Reflex	309.00	4.10°	-81.10°	Non					
Reflex	312.00	4.20°	-81.00°	Non					
Reflex	315.00	4.40°	-81.00°	Non					
Reflex	318.00	5.70°	-81.00°	Non					
Reflex	321.00	5.90°	-81.00°	Non					
Reflex	324.00	5.70°	-81.10°	Non					
Reflex	327.00	5.00°	-81.10°	Non					
Reflex	330.00	5.50°	-81.10°	Non					
Reflex	333.00	4.50°	-81.20°	Non					
Reflex	336.00	4.70°	-81.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.20	MT						
		<b>Mort-terrain</b>						
0.20	336.00	SY; POR	0.20	1.90	D014994	1.70	0.013	0.013
		<b>Syénite; Porphyrique</b>	1.90	3.50	D014995	1.60	0.017	0.017
		Porphyre syénitique carbonaté et hématisé.	3.50	5.00	D014996	1.50	0.026	0.026
			5.00	6.50	D014997	1.50	0.068	0.068
			6.50	8.00	D014998	1.50	0.016	0.016
			8.00	9.50	D014999	1.50	<0.005	0.001
			9.50	11.00	D022001	1.50	0.053	0.053
			11.00	12.50	D022002	1.50	0.016	0.016
			12.50	14.00	D022003	1.50	0.046	0.046
			14.00	15.50	D022004	1.50	0.112	0.112
			15.50	17.00	D022006	1.50	0.047	0.047
			17.00	18.50	D022007	1.50	0.005	0.005
			18.50	20.00	D022008	1.50	0.051	0.051
			20.00	21.50	D022009	1.50	0.402	0.402
			21.50	23.00	D022010	1.50	0.037	0.037
			23.00	24.50	D022011	1.50	0.015	0.015
			24.50	26.00	D022012	1.50	0.094	0.094
			26.00	27.50	D022013	1.50	0.096	0.096
			27.50	29.00	D022014	1.50	0.077	0.077
			29.00	30.50	D022016	1.50	0.132	0.132
			30.50	32.00	D022017	1.50	0.210	0.210
			32.00	33.50	D022018	1.50	0.273	0.273
			33.50	35.00	D022019	1.50	0.110	0.110
			35.00	36.50	D022020	1.50	0.620	0.620
			36.50	38.00	D022021	1.50	0.165	0.165
			38.00	39.50	D022022	1.50	0.008	0.008
			39.50	41.00	D022023	1.50	0.027	0.027
			41.00	42.50	D022024	1.50	0.043	0.043
			42.50	44.00	D022026	1.50	0.047	0.047
			44.00	45.50	D022027	1.50	0.254	0.254
			45.50	47.00	D022028	1.50	0.167	0.167
			47.00	48.50	D022029	1.50	0.310	0.310

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.50	50.00	D022030	1.50	0.109		0.109
	50.00	51.50	D022031	1.50	0.057		0.057
	51.50	53.00	D022032	1.50	0.031		0.031
	53.00	54.50	D022033	1.50	0.026		0.026
	54.50	56.00	D022034	1.50	0.018		0.018
	56.00	57.50	D022036	1.50	0.006		0.006
	57.50	59.00	D022037	1.50	0.071		0.071
	59.00	60.50	D022038	1.50	0.009		0.009
	60.50	62.00	D022039	1.50	0.024		0.024
	62.00	63.50	D022041	1.50	0.024		0.024
	63.50	65.00	D022042	1.50	0.019		0.019
	65.00	66.50	D022043	1.50	0.023		0.023
	66.50	68.00	D022044	1.50	0.025		0.025
	68.00	69.50	D022046	1.50	0.085		0.085
	69.50	71.00	D022047	1.50	0.006		0.006
	71.00	72.50	D022048	1.50	0.006		0.006
	72.50	74.00	D022049	1.50	0.006		0.006
	74.00	75.50	D022050	1.50	0.046		0.046
	75.50	77.00	D022051	1.50	0.049		0.049
	77.00	78.50	D022052	1.50	<0.005		0.001
	78.50	80.00	D022053	1.50	0.006		0.006
	80.00	81.50	D022054	1.50	0.007		0.007
	81.50	83.00	D022056	1.50	0.006		0.006
	83.00	84.50	D022057	1.50	0.030		0.030
	84.50	86.00	D022058	1.50	0.103		0.103
	86.00	87.50	D022059	1.50	0.073		0.073
	87.50	89.00	D022060	1.50	0.269		0.269
	89.00	90.50	D022061	1.50	0.028		0.028
	90.50	92.00	D022062	1.50	0.021		0.021
	92.00	93.50	D022063	1.50	0.195		0.195
	93.50	95.00	D022064	1.50	0.026		0.026
	95.00	96.50	D022066	1.50	0.005		0.005
	96.50	98.00	D022067	1.50	0.068		0.068

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.00	99.50	D022068	1.50	0.057		0.057
	99.50	101.00	D022069	1.50	0.014		0.014
	101.00	102.50	D022070	1.50	0.021		0.021
	102.50	104.00	D022071	1.50	1.645		1.645
	104.00	105.50	D022072	1.50	0.713		0.713
	105.50	107.00	D022073	1.50	0.841		0.841
	107.00	108.50	D022074	1.50	0.150		0.150
	108.50	110.00	D022076	1.50	0.060		0.060
	110.00	111.00	D022077	1.00	0.444		0.444
	111.00	112.50	D022078	1.50	2.250		2.250
	112.50	114.00	D022079	1.50	3.680		3.680
	114.00	115.50	D022081	1.50	3.120		3.120
	115.50	117.00	D022082	1.50	2.830		2.830
	117.00	118.50	D022083	1.50	0.172		0.172
	118.50	120.00	D022084	1.50	0.187		0.187
	120.00	121.50	D022086	1.50	<0.005		0.001
	121.50	123.00	D022087	1.50	<0.005		0.001
	123.00	124.50	D022088	1.50	0.007		0.007
	124.50	126.00	D022089	1.50	0.049		0.049
	126.00	127.50	D022090	1.50	0.341		0.341
	127.50	129.00	D022091	1.50	0.350		0.350
	129.00	130.50	D022092	1.50	0.426		0.426
	130.50	132.00	D022093	1.50	0.248		0.248
	132.00	133.50	D022094	1.50	0.009		0.009
	133.50	135.00	D022096	1.50	0.022		0.022
	135.00	136.50	D022097	1.50	0.032		0.032
	136.50	138.00	D022098	1.50	<0.005		0.001
	138.00	139.50	D022099	1.50	<0.005		0.001
	139.50	141.00	D022100	1.50	0.006		0.006
	141.00	142.50	D022101	1.50	<0.005		0.001
	142.50	144.00	D022102	1.50	0.005		0.005
	144.00	145.50	D022103	1.50	0.253		0.253
	145.50	147.00	D022104	1.50	0.131		0.131

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.00	148.50	D022106	1.50	0.088		0.088
	148.50	150.00	D022107	1.50	<0.005		0.001
	150.00	151.50	D022108	1.50	0.005		0.005
	151.50	153.00	D022109	1.50	<0.005		0.001
	153.00	154.50	D022110	1.50	0.008		0.008
	154.50	156.00	D022111	1.50	0.005		0.005
	156.00	157.50	D022112	1.50	<0.005		0.001
	157.50	159.00	D022113	1.50	<0.005		0.001
	159.00	160.50	D022114	1.50	<0.005		0.001
	160.50	162.00	D022116	1.50	0.017		0.017
	162.00	163.50	D022117	1.50	<0.005		0.001
	163.50	165.00	D022118	1.50	0.023		0.023
	165.00	166.50	D022119	1.50	0.010		0.010
	166.50	168.00	D022121	1.50	0.090		0.090
	168.00	169.50	D022122	1.50	0.089		0.089
	169.50	171.00	D022123	1.50	0.139		0.139
	171.00	172.50	D022124	1.50	0.180		0.180
	172.50	174.00	D022126	1.50	0.157		0.157
	174.00	175.50	D022127	1.50	0.489		0.489
	175.50	177.00	D022128	1.50	0.368		0.368
	177.00	178.50	D022129	1.50	0.053		0.053
	178.50	180.00	D022130	1.50	0.422		0.422
	180.00	181.50	D022131	1.50	0.576		0.576
	181.50	183.00	D022132	1.50	0.878		0.878
	183.00	184.50	D022133	1.50	0.075		0.075
	184.50	186.00	D022134	1.50	0.008		0.008
	186.00	187.50	D022136	1.50	0.005		0.005
	187.50	189.00	D022137	1.50	<0.005		0.001
	189.00	190.50	D022138	1.50	<0.005		0.001
	190.50	192.00	D022139	1.50	<0.005		0.001
	192.00	193.50	D022140	1.50	<0.005		0.001
	193.50	195.00	D022141	1.50	0.005		0.005
	195.00	196.50	D022142	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	196.50	198.00	D022143	1.50	0.056		0.056
	198.00	199.50	D022144	1.50	0.034		0.034
	199.50	201.00	D022146	1.50	0.089		0.089
	201.00	202.50	D022147	1.50	0.007		0.007
	202.50	204.00	D022148	1.50	0.006		0.006
	204.00	205.50	D022149	1.50	0.038		0.038
	205.50	207.00	D022150	1.50	<0.005		0.001
	207.00	208.50	D022151	1.50	<0.005		0.001
	208.50	210.00	D022152	1.50	<0.005		0.001
	210.00	211.50	D022153	1.50	0.042		0.042
	211.50	213.00	D022154	1.50	0.008		0.008
	213.00	214.50	D022156	1.50	0.141		0.141
	214.50	216.00	D022157	1.50	0.024		0.024
	216.00	217.50	D022158	1.50	<0.005		0.001
	217.50	219.00	D022159	1.50	<0.005		0.001
	219.00	220.50	D022161	1.50	0.006		0.006
	220.50	222.00	D022162	1.50	0.005		0.005
	222.00	223.50	D022163	1.50	0.012		0.012
	223.50	225.00	D022164	1.50	0.007		0.007
	225.00	226.50	D022166	1.50	<0.005		0.001
	226.50	228.00	D022167	1.50	0.065		0.065
	228.00	229.50	D022168	1.50	<0.005		0.001
	229.50	231.00	D022169	1.50	<0.005		0.001
	231.00	232.50	D022170	1.50	<0.005		0.001
	232.50	234.00	D022171	1.50	<0.005		0.001
	234.00	235.50	D022172	1.50	0.058		0.058
	235.50	237.00	D022173	1.50	0.170		0.170
	237.00	238.50	D022174	1.50	0.129		0.129
	238.50	240.00	D022176	1.50	0.314		0.314
	240.00	241.00	D022177	1.00	0.547		0.547
	241.00	242.00	D022178	1.00	0.515		0.515
	242.00	243.50	D022179	1.50	0.381		0.381
	243.50	245.00	D022180	1.50	2.340		2.340



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	245.00	246.50	D022181	1.50	0.056		0.056	
	246.50	248.00	D022182	1.50	0.166		0.166	
	248.00	249.50	D022183	1.50	0.006		0.006	
	249.50	251.00	D022184	1.50	<0.005		0.001	
	251.00	252.50	D022186	1.50	0.032		0.032	
	252.50	254.00	D022187	1.50	<0.005		0.001	
	254.00	255.50	D022188	1.50	0.144		0.144	
	255.50	257.00	D022189	1.50	0.265		0.265	
	257.00	258.50	D022190	1.50	0.057		0.057	
	258.50	260.00	D022191	1.50	0.406		0.406	
	260.00	261.50	D022192	1.50	0.535		0.535	
	261.50	263.00	D022193	1.50	1.795		1.795	
	263.00	264.50	D022194	1.50	0.282		0.282	
	264.50	266.00	D022196	1.50	0.873		0.873	
	266.00	267.50	D022197	1.50	0.585		0.585	
	267.50	269.00	D022198	1.50	0.019		0.019	
	269.00	270.50	D022199	1.50	0.193		0.193	
	270.50	272.00	D022200	1.50	<0.005		0.001	
	272.00	273.50	D022201	1.50	0.120		0.120	
	273.50	275.00	D022202	1.50	0.018		0.018	
	275.00	276.70	D022203	1.70	0.177		0.177	
	276.70	278.40	D022204	1.70	<0.005		0.001	
278.40	286.20	PT	278.40	280.00	D022206	1.60	<0.005	0.001
		<b>Porphyre trachytique</b>	280.00	281.50	D022207	1.50	<0.005	0.001
		Rose-beige à rose-verdâtre, hématisé et épidotisé,	281.50	283.00	D022208	1.50	<0.005	0.001
		phénocristaux orientés à 0-20°.	283.00	284.50	D022209	1.50	2.600	2.600
			284.50	286.20	D022210	1.70	2.660	2.660
			286.20	287.20	D022211	1.00	0.033	0.033
			287.20	288.40	D022212	1.20	0.021	0.021
			288.40	290.00	D022213	1.60	<0.005	0.001
			290.00	291.60	D022214	1.60	0.214	0.214
			291.60	293.00	D022216	1.40	0.073	0.073
			293.00	294.50	D022217	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	294.50	296.00	D022218	1.50	0.170		0.170
	296.00	297.50	D022219	1.50	0.268		0.268
	297.50	299.00	D022220	1.50	0.029		0.029
	299.00	300.50	D022221	1.50	0.081		0.081
	300.50	302.00	D022222	1.50	0.036		0.036
	302.00	303.40	D022223	1.40	0.020		0.020
	303.40	304.40	D022224	1.00	0.032		0.032
	304.40	306.00	D022226	1.60	0.044		0.044
	306.00	307.50	D022227	1.50	<0.005		0.001
	307.50	309.00	D022228	1.50	0.006		0.006
	309.00	310.50	D022229	1.50	0.007		0.007
	310.50	312.00	D022230	1.50	0.005		0.005
	312.00	313.50	D022231	1.50	0.018		0.018
	313.50	315.00	D022232	1.50	0.010		0.010
	315.00	316.50	D022233	1.50	0.010		0.010
	316.50	318.00	D022234	1.50	0.011		0.011
	318.00	319.50	D022236	1.50	0.011		0.011
	319.50	321.00	D022237	1.50	0.012		0.012
	321.00	322.50	D022238	1.50	0.030		0.030
	322.50	324.00	D022239	1.50	0.014		0.014
	324.00	325.50	D022241	1.50	0.012		0.012
	325.50	327.00	D022242	1.50	0.006		0.006
	327.00	328.50	D022243	1.50	0.007		0.007
	328.50	330.00	D022244	1.50	0.009		0.009
	330.00	331.50	D022246	1.50	<0.005		0.001
	331.50	333.00	D022247	1.50	0.005		0.005
	333.00	334.50	D022248	1.50	<0.005		0.001
	334.50	336.00	D022249	1.50	<0.005		0.001
336.00	Fin du sondage						
	Nombre d'échantillons : 225						
	Nombre d'échantillons QAQC : 31						
	Longueur totale échantillonnée : 335.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
8.00	8.00	D015000	M1	0.00	<0.005	0.001
14.00	15.50	D022005	D022004	1.50	0.166	0.166
27.50	27.50	D022015	L	0.00	2.160	2.160
41.00	42.50	D022025	D022024	1.50	0.037	0.037
54.50	54.50	D022035	M	0.00	3.050	3.050
60.50	60.50	D022040	M1	0.00	0.005	0.005
66.50	68.00	D022045	D022044	1.50	0.029	0.029
80.00	80.00	D022055	J	0.00	0.731	0.731
93.50	95.00	D022065	D022064	1.50	0.016	0.016
107.00	107.00	D022075	M	0.00	3.140	3.140
112.50	112.50	D022080	M1	0.00	<0.005	0.001
118.50	120.00	D022085	D022084	1.50	0.280	0.280
132.00	132.00	D022095	J	0.00	0.773	0.773
145.50	147.00	D022105	D022104	1.50	0.133	0.133
159.00	159.00	D022115	K	0.00	1.045	1.045
165.00	165.00	D022120	M1	0.00	<0.005	0.001
171.00	172.50	D022125	D022124	1.50	0.197	0.197
184.50	184.50	D022135	L	0.00	2.170	2.170
198.00	199.50	D022145	D022144	1.50	0.038	0.038
211.50	211.50	D022155	M	0.00	3.010	3.010
217.50	217.50	D022160	M1	0.00	<0.005	0.001
223.50	225.00	D022165	D022164	1.50	0.008	0.008
237.00	237.00	D022175	J	0.00	0.740	0.740
249.50	251.00	D022185	D022184	1.50	<0.005	0.001
263.00	263.00	D022195	K	0.00	1.035	1.035
276.70	278.40	D022205	D022204	1.70	<0.005	0.001
290.00	290.00	D022215	J	0.00	0.701	0.701
303.40	304.40	D022225	D022224	1.00	0.033	0.033
316.50	316.50	D022235	K	0.00	1.135	1.135
322.50	322.50	D022240	M1	0.00	0.007	0.007
328.50	328.50	D022245	L	0.00	2.230	2.230

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-180</b>	Titre minier :	Section :	630300
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-05-27	Date de description :	2010-06-12
	Au : 2010-05-31		

Collet

Azimut : 176.00°  
 Plongée : -51.00°  
 Longueur : 116.00 m

UTM

Est	630 295.6
Nord	5 374 220.6
Élévation	308.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	177.50°	-51.40°	Non
Reflex	8.00	178.20°	-51.40°	Non
Reflex	11.00	178.50°	-51.40°	Non
Reflex	14.00	177.80°	-51.40°	Non
Reflex	17.00	177.00°	-51.40°	Non
Reflex	20.00	175.70°	-51.40°	Oui
Reflex	23.00	178.50°	-51.30°	Non
Reflex	26.00	178.10°	-51.30°	Non
Reflex	29.00	177.60°	-51.20°	Non
Reflex	32.00	178.40°	-51.30°	Non
Reflex	35.00	178.50°	-51.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	181.60°	-51.10°	Oui
Reflex	41.00	178.70°	-51.00°	Non
Reflex	44.00	179.00°	-51.00°	Non
Reflex	47.00	178.50°	-51.00°	Non
Reflex	50.00	179.80°	-50.90°	Non
Reflex	53.00	179.40°	-50.90°	Non
Reflex	56.00	178.30°	-50.80°	Non
Reflex	59.00	179.10°	-50.70°	Non
Reflex	62.00	179.40°	-50.60°	Non
Reflex	65.00	179.20°	-50.50°	Non
Reflex	68.00	179.30°	-50.40°	Non
Reflex	71.00	179.60°	-50.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	179.40°	-50.20°	Non					
Reflex	77.00	179.60°	-50.10°	Non					
Reflex	80.00	179.90°	-49.90°	Non					
Reflex	83.00	179.80°	-49.80°	Non					
Reflex	86.00	179.80°	-49.80°	Non					
Reflex	89.00	180.00°	-49.70°	Non					
Reflex	92.00	180.20°	-49.70°	Non					
Reflex	95.00	180.00°	-49.70°	Non					
Reflex	98.00	180.40°	-49.60°	Non					
Reflex	101.00	180.20°	-49.60°	Non					
Reflex	104.00	180.40°	-49.60°	Non					
Reflex	107.00	180.50°	-49.60°	Non					
Reflex	110.00	180.50°	-49.60°	Non					
Reflex	113.00	180.50°	-49.60°	Non					
Reflex	116.00	180.50°	-49.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	0.40	MT						
		<b>Mort-terrain</b>						
0.40	58.00	SY; MAS; FIN; MTY	0.40	2.00	D004940	1.60	0.037	0.037
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	2.00	3.50	D004941	1.50	0.052	0.052
		grenue, grains moyen à fin, hématisation sericitisation, altération en calcite, oxydes de carbonates, SR+, HM+++, ++ magnétique	3.50	5.00	D004942	1.50	0.068	0.068
			5.00	6.50	D004943	1.50	0.117	0.117
			6.50	8.00	D004944	1.50	0.286	0.286
			8.00	9.50	D004945	1.50	0.096	0.096
			9.50	11.00	D004946	1.50	0.111	0.111
			11.00	12.50	D004947	1.50	0.039	0.039
			12.50	14.00	D004948	1.50	0.053	0.053
			14.00	15.50	D004950	1.50	0.777	0.777
			15.50	17.00	D004951	1.50	1.075	1.075
			17.00	18.50	D004952	1.50	1.060	1.060
			18.50	20.00	D004953	1.50	0.761	0.761
			20.00	21.50	D004954	1.50	0.479	0.479
			21.50	23.00	D004955	1.50	0.229	0.229
			23.00	24.50	D004956	1.50	0.211	0.211
			24.50	26.00	D004957	1.50	0.127	0.127
			26.00	27.50	D004958	1.50	0.228	0.228
			27.50	29.00	D004960	1.50	0.943	0.943
			29.00	30.50	D004961	1.50	0.497	0.497
			30.50	32.00	D004962	1.50	0.621	0.621
			32.00	33.50	D004963	1.50	0.552	0.552
			33.50	35.00	D004964	1.50	0.045	0.045
			35.00	36.50	D004965	1.50	1.335	1.335
			36.50	38.00	D004966	1.50	0.203	0.203
			38.00	39.50	D004967	1.50	0.018	0.018
			39.50	41.00	D004968	1.50	0.025	0.025
			41.00	42.50	D004970	1.50	0.062	0.062
			42.50	44.00	D004971	1.50	0.057	0.057
			44.00	45.50	D004972	1.50	0.028	0.028
			45.50	47.00	D004973	1.50	0.015	0.015
			47.00	48.50	D004974	1.50	0.025	0.025

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
58.00	105.50	TU; FIN  <b>Tuf à cendre/lapillis 40°; Grains fins</b> fin à très fin, lité, laminé et schisteux, intercalation de fragments de QZ mm-cm, altération en chlorite et séricite, + calcite, PY automorphe et fine irrég diss	48.50	50.00	D004975	1.50	<0.005		0.001
			50.00	51.50	D004977	1.50	0.018		0.018
			51.50	53.00	D004978	1.50	0.315		0.315
			53.00	54.50	D004980	1.50	1.345		1.345
			54.50	56.00	D004981	1.50	0.009		0.009
			56.00	57.00	D004982	1.00	0.024		0.024
			57.00	58.00	D004983	1.00	0.019		0.019
			58.00	59.50	D004984	1.50	0.122		0.122
			59.50	61.00	D004985	1.50	0.279		0.279
			61.00	62.50	D004986	1.50	0.333		0.333
			62.50	64.00	D004987	1.50	0.285		0.285
			64.00	65.50	D004988	1.50	0.065		0.065
			65.50	67.00	D004990	1.50	0.521		0.521
			67.00	68.50	D004991	1.50	0.392		0.392
			68.50	70.00	D004992	1.50	0.352		0.352
70.00	71.50	D004993	1.50	0.330		0.330			
71.50	73.00	D004994	1.50	0.217		0.217			
73.00	74.50	D004995	1.50	0.301		0.301			
58.00	67.00	CIS <b>Cisaillement 70°</b>							
74.50	88.00	CIS <b>Cisaillement 50°</b>							
			74.50	76.00	D004996	1.50	0.062		0.062
			76.00	77.50	D004997	1.50	0.269		0.269
			77.50	79.00	D004998	1.50	0.408		0.408
			79.00	80.50	D005000	1.50	0.104		0.104
			80.50	82.00	D027001	1.50	0.225		0.225
			82.00	83.50	D027002	1.50	0.132		0.132
			83.50	85.00	D027003	1.50	0.114		0.114
			85.00	86.50	D027004	1.50	0.069		0.069
			86.50	88.00	D027005	1.50	0.270		0.270
			88.00	89.50	D027006	1.50	0.094		0.094
88.50	88.60	FAI <b>Faille 60°</b> boue de faille verdâtre	89.50	91.00	D027007	1.50	0.133		0.133
			91.00	92.50	D027008	1.50	0.012		0.012
			92.50	94.00	D027010	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
94.10	94.12	FAI <b>Faille 50°</b> boue verdâtre	94.00	95.50	D027011	1.50	0.010		0.010
			95.50	97.00	D027012	1.50	0.009		0.009
			97.00	98.50	D027013	1.50	0.019		0.019
			98.50	100.00	D027014	1.50	0.038		0.038
			100.00	101.50	D027015	1.50	0.012		0.012
			101.50	103.00	D027017	1.50	0.008		0.008
			103.00	104.00	D027018	1.00	0.006		0.006
			104.00	105.50	D027020	1.50	0.013		0.013
			105.50	110.00	GR; MAS; FIN <b>Grès 40°; Roche massive; Grains fins</b> grenue à grains fins avec passage de mudstone en fin d'éch, CL++, BO+, +calcite	105.50	107.00	D027021	1.50
107.00	108.50	D027022				1.50	0.009		0.009
108.50	110.00	D027023				1.50	<0.005		0.001
109.90	110.00	FAI <b>Faille 40°</b>							
110.00	115.00	TU; FIN; RUB; LAM <b>Tuf à cendre/lapillis 50°; Grains fins; Rubané; Laminations parallèles</b> laminations 40-60° ac, cheveux et veinules de carbonâtes 30-40° ac, CL++ SR+, oxydes de carbonâtes, localement fragments de QZ mm,	110.00	111.50	D027024	1.50	0.005		0.005
			111.50	113.00	D027025	1.50	<0.005		0.001
			113.00	114.50	D027026	1.50	<0.005		0.001
			114.50	116.00	D027027	1.50	0.005		0.005
115.00	116.00	GR; MAS; FIN <b>Grès 40°; Roche massive; Grains fins</b> grenue à grains fin, altération en chlorite veines de QZ carbonaté							
116.00	<b>Fin du sondage</b> Nombre d'échantillons : 78 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 115.60								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.50	14.00	D004949	D004948	1.50	0.053	0.053
26.00	26.00	D004959	J	0.00	0.747	0.747
39.50	41.00	D004969	D004968	1.50	0.024	0.024
48.50	48.50	D004976	M1	0.00	<0.005	0.001
51.50	51.50	D004979	K	0.00	1.065	1.065
64.00	65.50	D004989	D004988	1.50	0.069	0.069
77.50	77.50	D004999	L	0.00	2.230	2.230
91.00	92.50	D027009	D027008	1.50	0.014	0.014
100.00	100.00	D027016	M1	0.00	<0.005	0.001
103.00	103.00	D027019	M	0.00	2.960	2.960

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-181**

Titre minier :

Section :                      630500

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :

Lot :

Du :                              2010-04-26

Date de description :        2010-06-04

Au :                              2010-05-13

Collet

UTM

Azimut :                      0.00°

Plongée :                      -60.00°

Longueur :                    467.00 m

Est                              630 499.6

Nord                            5 374 199.5

Élévation                      307.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	3.70°	-61.50°	Oui
Reflex	8.00	353.90°	-61.10°	Oui
Reflex	11.00	0.40°	-61.10°	Non
Reflex	14.00	1.70°	-61.10°	Oui
Reflex	17.00	0.70°	-61.10°	Non
Reflex	20.00	359.90°	-61.10°	Non
Reflex	23.00	0.30°	-61.00°	Non
Reflex	26.00	0.50°	-61.10°	Non
Reflex	29.00	0.80°	-61.00°	Non
Reflex	32.00	0.40°	-61.00°	Non
Reflex	35.00	0.90°	-61.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.90°	-61.10°	Non
Reflex	41.00	2.00°	-61.10°	Non
Reflex	44.00	2.30°	-61.10°	Non
Reflex	47.00	3.50°	-61.10°	Oui
Reflex	50.00	2.80°	-61.10°	Non
Reflex	53.00	2.60°	-61.10°	Non
Reflex	56.00	2.90°	-61.20°	Non
Reflex	59.00	2.60°	-61.20°	Non
Reflex	62.00	3.30°	-61.20°	Non
Reflex	65.00	2.90°	-61.20°	Non
Reflex	68.00	3.30°	-61.20°	Non
Reflex	71.00	4.60°	-61.10°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	4.50°	-61.20°	Non	Reflex	173.00	8.50°	-61.50°	Non
Reflex	77.00	4.00°	-61.20°	Non	Reflex	176.00	8.40°	-61.40°	Non
Reflex	80.00	3.60°	-61.20°	Non	Reflex	179.00	6.10°	-61.40°	Non
Reflex	83.00	6.00°	-61.20°	Oui	Reflex	182.00	6.10°	-61.40°	Non
Reflex	86.00	4.30°	-61.30°	Non	Reflex	185.00	6.90°	-61.40°	Non
Reflex	89.00	5.70°	-61.30°	Non	Reflex	188.00	7.30°	-61.30°	Non
Reflex	92.00	5.90°	-61.30°	Non	Reflex	191.00	7.50°	-61.30°	Non
Reflex	95.00	6.20°	-61.30°	Non	Reflex	194.00	7.60°	-61.30°	Non
Reflex	98.00	6.40°	-61.30°	Non	Reflex	197.00	7.10°	-61.30°	Non
Reflex	101.00	6.20°	-61.30°	Non	Reflex	200.00	8.30°	-61.20°	Oui
Reflex	104.00	6.00°	-61.30°	Non	Reflex	203.00	7.40°	-61.20°	Non
Reflex	107.00	5.60°	-61.30°	Non	Reflex	206.00	6.50°	-61.20°	Non
Reflex	110.00	5.90°	-61.40°	Non	Reflex	209.00	6.80°	-61.20°	Non
Reflex	113.00	4.80°	-61.20°	Oui	Reflex	212.00	7.40°	-61.30°	Non
Reflex	116.00	5.80°	-61.30°	Non	Reflex	215.00	7.70°	-61.30°	Non
Reflex	119.00	6.50°	-61.30°	Non	Reflex	218.00	7.30°	-61.30°	Non
Reflex	122.00	5.60°	-61.40°	Non	Reflex	221.00	7.60°	-61.30°	Non
Reflex	125.00	6.30°	-61.30°	Non	Reflex	224.00	7.60°	-61.20°	Non
Reflex	128.00	7.00°	-61.40°	Non	Reflex	227.00	7.60°	-61.10°	Non
Reflex	131.00	6.20°	-61.40°	Non	Reflex	230.00	8.50°	-61.10°	Non
Reflex	134.00	6.90°	-61.30°	Non	Reflex	233.00	9.10°	-61.10°	Non
Reflex	137.00	6.20°	-61.30°	Non	Reflex	236.00	8.40°	-61.10°	Non
Reflex	140.00	2.20°	-61.30°	Oui	Reflex	239.00	7.80°	-61.10°	Non
Reflex	143.00	7.30°	-61.40°	Non	Reflex	242.00	9.00°	-61.10°	Non
Reflex	146.00	7.20°	-61.40°	Non	Reflex	245.00	9.10°	-61.20°	Non
Reflex	149.00	7.10°	-61.40°	Non	Reflex	248.00	9.10°	-61.20°	Non
Reflex	152.00	9.10°	-61.40°	Oui	Reflex	251.00	8.80°	-61.20°	Non
Reflex	155.00	7.40°	-61.40°	Non	Reflex	254.00	9.10°	-61.20°	Non
Reflex	158.00	8.00°	-61.40°	Oui	Reflex	257.00	9.60°	-61.30°	Non
Reflex	161.00	6.80°	-61.40°	Non	Reflex	260.00	9.70°	-61.30°	Non
Reflex	164.00	7.30°	-61.40°	Non	Reflex	263.00	10.00°	-61.40°	Non
Reflex	167.00	7.70°	-61.40°	Non	Reflex	266.00	10.00°	-61.30°	Non
Reflex	170.00	8.10°	-61.40°	Non	Reflex	269.00	10.20°	-61.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	9.40°	-61.40°	Non	Reflex	371.00	15.10°	-61.80°	Non
Reflex	275.00	9.80°	-61.40°	Non	Reflex	374.00	13.60°	-61.90°	Non
Reflex	278.00	10.90°	-61.50°	Non	Reflex	377.00	14.10°	-61.90°	Non
Reflex	281.00	12.30°	-61.50°	Oui	Reflex	380.00	15.30°	-61.90°	Non
Reflex	284.00	11.90°	-61.50°	Non	Reflex	383.00	14.90°	-61.90°	Non
Reflex	287.00	12.30°	-61.50°	Non	Reflex	386.00	14.70°	-61.90°	Non
Reflex	290.00	9.90°	-61.50°	Non	Reflex	389.00	14.60°	-61.90°	Non
Reflex	293.00	10.20°	-61.50°	Non	Reflex	392.00	15.60°	-61.80°	Non
Reflex	296.00	11.40°	-61.70°	Non	Reflex	395.00	15.60°	-61.80°	Non
Reflex	299.00	10.00°	-61.60°	Non	Reflex	398.00	16.20°	-61.80°	Non
Reflex	302.00	12.40°	-61.60°	Non	Reflex	401.00	16.10°	-61.70°	Non
Reflex	305.00	9.60°	-61.60°	Oui	Reflex	404.00	16.10°	-61.70°	Non
Reflex	308.00	9.90°	-61.70°	Oui	Reflex	407.00	15.00°	-61.70°	Non
Reflex	311.00	12.30°	-61.70°	Non	Reflex	410.00	16.80°	-61.60°	Non
Reflex	314.00	12.10°	-61.80°	Non	Reflex	413.00	15.80°	-61.60°	Non
Reflex	317.00	12.10°	-61.70°	Non	Reflex	416.00	16.60°	-61.50°	Non
Reflex	320.00	12.30°	-61.80°	Non	Reflex	419.00	16.80°	-61.60°	Non
Reflex	323.00	13.70°	-61.80°	Non	Reflex	422.00	17.30°	-61.50°	Non
Reflex	326.00	12.50°	-61.80°	Non	Reflex	425.00	16.30°	-61.50°	Non
Reflex	329.00	13.90°	-61.80°	Non	Reflex	428.00	14.50°	-61.50°	Non
Reflex	332.00	13.20°	-61.80°	Non	Reflex	431.00	17.10°	-61.50°	Non
Reflex	335.00	13.10°	-61.80°	Non	Reflex	434.00	17.80°	-61.50°	Non
Reflex	338.00	13.40°	-61.90°	Non	Reflex	437.00	18.10°	-61.50°	Non
Reflex	341.00	13.90°	-61.80°	Non	Reflex	440.00	17.60°	-61.40°	Non
Reflex	344.00	13.20°	-61.80°	Non	Reflex	443.00	17.90°	-61.40°	Non
Reflex	347.00	13.20°	-61.80°	Non	Reflex	446.00	18.50°	-61.30°	Non
Reflex	350.00	13.70°	-61.80°	Non	Reflex	449.00	18.20°	-61.20°	Non
Reflex	353.00	14.30°	-61.80°	Non	Reflex	452.00	19.30°	-61.20°	Non
Reflex	356.00	13.80°	-61.80°	Non	Reflex	455.00	18.10°	-61.10°	Non
Reflex	359.00	13.90°	-61.80°	Non	Reflex	458.00	18.10°	-61.00°	Non
Reflex	362.00	13.50°	-61.80°	Non	Reflex	461.00	16.00°	-61.00°	Non
Reflex	365.00	13.90°	-61.90°	Non	Reflex	464.00	14.10°	-60.90°	Non
Reflex	368.00	14.80°	-61.90°	Non	Reflex	467.00	14.40°	-60.90°	Non

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	6.30	MT						
		<b>Mort-terrain</b>						
6.30	135.70	SY; MAS; FIN; MTY	6.30	8.00	D004249	1.70	0.096	0.096
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	8.00	9.50	D004250	1.50	0.571	0.571
		grenue à grains moyen à fin, localement phénocristaux de FP	9.50	11.00	D004251	1.50	0.212	0.212
		millimétrique, passages à altération en calcite, oxydes de carbonâtes,	11.00	12.50	D004252	1.50	2.130	2.130
		hématisation	12.50	14.00	D004253	1.50	2.220	2.220
			14.00	15.50	D004254	1.50	1.120	1.120
			15.50	17.00	D004255	1.50	1.100	1.100
16.30	18.50	FRC	17.00	18.50	D004256	1.50	1.410	1.410
		<b>Fracturé</b>	18.50	20.00	D004257	1.50	0.314	0.314
		fragment mêlés cm	20.00	21.50	D004259	1.50	0.090	0.090
			21.50	23.00	D004260	1.50	0.152	0.152
			23.00	24.50	D004261	1.50	0.649	0.649
			24.50	26.00	D004262	1.50	1.330	1.330
			26.00	27.50	D004263	1.50	1.745	1.745
			27.50	29.00	D004264	1.50	1.710	1.710
			29.00	30.50	D004265	1.50	1.090	1.090
			30.50	32.00	D004266	1.50	0.230	0.230
			32.00	33.50	D004267	1.50	0.656	0.656
			33.50	35.00	D004269	1.50	0.230	0.230
			35.00	36.50	D004270	1.50	0.319	0.319
			36.50	38.00	D004271	1.50	0.052	0.052
			38.00	39.50	D004272	1.50	0.062	0.062
			39.50	41.00	D004273	1.50	0.019	0.019
			41.00	42.50	D004274	1.50	<0.005	0.001
			42.50	44.00	D004275	1.50	<0.005	0.001
			44.00	45.50	D004276	1.50	0.007	0.007
			45.50	47.00	D004277	1.50	<0.005	0.001
			47.00	48.50	D004279	1.50	<0.005	0.001
			48.50	50.00	D004280	1.50	0.006	0.006
			50.00	51.50	D004281	1.50	0.243	0.243
			51.50	53.00	D004282	1.50	0.270	0.270

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
89.00      135.70      SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi, 0.2-2 cm localement zoné	53.00	54.50	D004283	1.50	0.185		0.185
	54.50	56.00	D004284	1.50	0.078		0.078
	56.00	57.50	D004286	1.50	0.083		0.083
	57.50	59.00	D004287	1.50	0.011		0.011
	59.00	60.50	D004289	1.50	0.108		0.108
	60.50	62.00	D004290	1.50	0.535		0.535
	62.00	63.50	D004291	1.50	0.023		0.023
	63.50	65.00	D004292	1.50	0.037		0.037
	65.00	66.50	D004293	1.50	0.072		0.072
	66.50	68.00	D004294	1.50	0.021		0.021
	68.00	69.50	D004295	1.50	<0.005		0.001
	69.50	71.00	D004296	1.50	<0.005		0.001
	71.00	72.50	D004297	1.50	0.176		0.176
	72.50	74.00	D004299	1.50	1.240		1.240
	74.00	75.50	D004300	1.50	0.887		0.887
	75.50	77.00	D004301	1.50	1.220		1.220
	77.00	78.50	D004302	1.50	0.098		0.098
	78.50	80.00	D004303	1.50	0.394		0.394
	80.00	81.50	D004304	1.50	0.280		0.280
	81.50	83.00	D004305	1.50	0.213		0.213
	83.00	84.50	D004306	1.50	0.075		0.075
	84.50	86.00	D004307	1.50	0.071		0.071
	86.00	87.50	D004309	1.50	0.034		0.034
	87.50	89.00	D004310	1.50	0.022		0.022
	89.00	90.50	D004311	1.50	0.021		0.021
	90.50	92.00	D004312	1.50	<0.005		0.001
	92.00	93.50	D004313	1.50	0.019		0.019
	93.50	95.00	D004314	1.50	<0.005		0.001
	95.00	96.50	D004315	1.50	<0.005		0.001
	96.50	98.00	D004316	1.50	0.020		0.020
98.00	99.50	D004317	1.50	0.085		0.085	
99.50	101.00	D004319	1.50	0.133		0.133	
101.00	102.50	D004320	1.50	0.007		0.007	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			102.50	104.00	D004321	1.50		0.026	0.026
			104.00	105.50	D004322	1.50		0.177	0.177
			105.50	107.00	D004323	1.50		0.319	0.319
			107.00	108.50	D004324	1.50		0.064	0.064
			108.50	110.00	D004326	1.50		0.033	0.033
			110.00	111.50	D004327	1.50		0.073	0.073
			111.50	113.00	D004329	1.50		0.021	0.021
			113.00	114.50	D004330	1.50		0.171	0.171
			114.50	116.00	D004331	1.50		0.223	0.223
			116.00	117.50	D004332	1.50		0.340	0.340
			117.50	119.00	D004333	1.50		0.195	0.195
			119.00	120.50	D004334	1.50		0.072	0.072
			120.50	122.00	D004335	1.50		0.125	0.125
			122.00	123.50	D004336	1.50		<0.005	0.001
			123.50	125.00	D004337	1.50		0.042	0.042
			125.00	126.50	D004339	1.50		<0.005	0.001
			126.50	128.00	D004340	1.50		0.065	0.065
			128.00	129.50	D004341	1.50		0.019	0.019
			129.50	131.00	D004342	1.50		0.005	0.005
			131.00	132.50	D004343	1.50		0.146	0.146
			132.50	134.00	D004344	1.50		<0.005	0.001
			134.00	135.70	D004345	1.70		0.062	0.062
135.70	136.00	NR							
		<b>Carotte perdue</b>							
136.00	163.50	SY; MAS; MTY; FIN	136.00	137.50	D004346	1.50		0.012	0.012
		<b>Syénite; Roche massive; Grains moyens; Grains fins</b>	137.50	139.00	D004347	1.50		0.037	0.037
		grenue à grains moyen à fin, altération en calcite fortement hématisé	139.00	140.50	D004349	1.50		0.006	0.006
			140.50	142.00	D004350	1.50		0.007	0.007
			142.00	143.50	D004351	1.50		<0.005	0.001
			143.50	145.00	D004352	1.50		<0.005	0.001
			145.00	146.50	D004353	1.50		<0.005	0.001
			146.50	148.00	D004354	1.50		<0.005	0.001
			148.00	149.50	D004355	1.50		<0.005	0.001
			149.50	151.00	D004356	1.50		0.008	0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
136.00	150.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi, 0.2-3 cm localement zoné	151.00	152.50	D004357	1.50	0.467		0.467
152.00	163.50	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi, 0.2-3 cm localement zoné	152.50	154.00	D004359	1.50	<0.005		0.001
			154.00	155.50	D004360	1.50	<0.005		0.001
			155.50	157.00	D004361	1.50	<0.005		0.001
			157.00	158.50	D004362	1.50	<0.005		0.001
			158.50	160.00	D004363	1.50	<0.005		0.001
			160.00	161.50	D004364	1.50	<0.005		0.001
			161.50	162.50	D004366	1.00	<0.005		0.001
			162.50	163.50	D004367	1.00	<0.005		0.001
163.50	163.90	NR <b>Carotte perdue</b>							
163.90	271.50	SY; MAS; FIN; MTY <b>Syénite; Roche massive; Grains fins; Grains moyens</b> grenue à grains moyen et fin, localement sub brêchique, CL+, HM+++, calcite	163.90	165.50	D004369	1.60	0.009		0.009
			165.50	167.00	D004370	1.50	<0.005		0.001
			167.00	168.50	D004371	1.50	<0.005		0.001
			168.50	170.00	D004372	1.50	<0.005		0.001
			170.00	171.50	D004373	1.50	<0.005		0.001
			171.50	173.00	D004374	1.50	<0.005		0.001
			173.00	174.50	D004375	1.50	<0.005		0.001
			174.50	176.00	D004376	1.50	0.104		0.104
			176.00	177.50	D004377	1.50	0.882		0.882
			177.50	179.00	D004379	1.50	0.008		0.008
			179.00	180.50	D004380	1.50	0.641		0.641
			180.50	182.00	D004381	1.50	<0.005		0.001
			182.00	183.50	D004382	1.50	<0.005		0.001
			183.50	185.00	D004383	1.50	0.063		0.063
			185.00	186.50	D004384	1.50	0.094		0.094
			186.50	188.00	D004385	1.50	<0.005		0.001
			188.00	189.50	D004386	1.50	<0.005		0.001
			189.50	191.00	D004387	1.50	<0.005		0.001
			191.00	192.50	D004389	1.50	0.022		0.022



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			192.50	194.00	D004390	1.50		0.026		0.026
			194.00	195.50	D004391	1.50		<0.005		0.001
			195.50	197.00	D004392	1.50		<0.005		0.001
			197.00	198.50	D004393	1.50		<0.005		0.001
			198.50	200.00	D004394	1.50		0.010		0.010
			200.00	201.50	D004395	1.50		<0.005		0.001
			201.50	203.00	D004396	1.50		<0.005		0.001
			203.00	204.50	D004397	1.50		<0.005		0.001
			204.50	206.00	D004399	1.50		<0.005		0.001
			206.00	207.50	D004400	1.50		<0.005		0.001
			207.50	209.00	D004401	1.50		<0.005		0.001
			209.00	210.50	D004402	1.50		<0.005		0.001
			210.50	212.00	D004403	1.50		<0.005		0.001
			212.00	213.50	D004404	1.50		<0.005		0.001
163.90	175.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux 0.3-2 cm, carbonâtes, chlorite hématite								
212.50	219.00	SY; POR <b>Syénite; Porphyrique</b> phenocristaux automorphe à sub automorphe ± 0.2-2 cm, HM++, Spécularite, CL+, Calcite	213.50	215.00	D004406	1.50		<0.005		0.001
			215.00	216.50	D004407	1.50		<0.005		0.001
			216.50	218.00	D004409	1.50		<0.005		0.001
			218.00	219.50	D004410	1.50		<0.005		0.001
			219.50	221.00	D004411	1.50		<0.005		0.001
			221.00	222.50	D004412	1.50		<0.005		0.001
			222.50	224.00	D004413	1.50		<0.005		0.001
			224.00	225.50	D004414	1.50		<0.005		0.001
			225.50	227.00	D004415	1.50		<0.005		0.001
			227.00	228.50	D004416	1.50		<0.005		0.001
228.00	271.50	SY; POR <b>Syénite; Porphyrique</b> induré, phénocristaux automorphe ± 0.2-1 cm zonée, CL+, HM++, calcite	228.50	230.00	D004417	1.50		0.005		0.005
			230.00	231.50	D004419	1.50		0.005		0.005
			231.50	233.00	D004420	1.50		0.007		0.007
			233.00	234.50	D004421	1.50		0.026		0.026
			234.50	236.00	D004422	1.50		<0.005		0.001
			236.00	237.50	D004423	1.50		<0.005		0.001
			237.50	239.00	D004424	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			239.00	240.50	D004425	1.50	<0.005		0.001
			240.50	242.00	D004426	1.50	<0.005		0.001
			242.00	243.50	D004427	1.50	<0.005		0.001
			243.50	245.00	D004429	1.50	<0.005		0.001
			245.00	246.50	D004430	1.50	<0.005		0.001
			246.50	248.00	D004431	1.50	<0.005		0.001
			248.00	249.50	D004432	1.50	0.024		0.024
			249.50	251.00	D004433	1.50	<0.005		0.001
			251.00	252.50	D004434	1.50	<0.005		0.001
			252.50	254.00	D004435	1.50	0.024		0.024
			254.00	255.50	D004436	1.50	<0.005		0.001
			255.50	256.60	D004437	1.10	<0.005		0.001
			256.60	258.00	D004439	1.40	0.276		0.276
			258.00	259.50	D004440	1.50	<0.005		0.001
			259.50	261.00	D004441	1.50	0.028		0.028
			261.00	262.50	D004442	1.50	<0.005		0.001
			262.50	264.00	D004443	1.50	<0.005		0.001
			264.00	265.50	D004444	1.50	<0.005		0.001
			265.50	267.00	D004446	1.50	<0.005		0.001
			267.00	268.50	D004447	1.50	<0.005		0.001
			268.50	270.00	D004449	1.50	0.012		0.012
			270.00	271.50	D004450	1.50	<0.005		0.001
271.50	272.00	NR							
		<b>Carotte perdue</b>							
272.00	467.00	SY; MAS; MTY; FIN	272.00	273.50	D004451	1.50	0.006		0.006
		<b>Syénite; Roche massive; Grains moyens; Grains fins</b>	273.50	275.00	D004452	1.50	<0.005		0.001
		grenue à grains moyen à fin, hématisation, localement chloritisé,	275.00	276.50	D004453	1.50	<0.005		0.001
		calcite, Séricite, spécularite	276.50	278.00	D004454	1.50	0.005		0.005
			278.00	279.50	D004455	1.50	0.006		0.006
			279.50	281.00	D004456	1.50	<0.005		0.001
			281.00	282.50	D004457	1.50	<0.005		0.001
			282.50	284.00	D004459	1.50	<0.005		0.001
			284.00	285.50	D004460	1.50	0.010		0.010
			285.50	287.00	D004461	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			287.00	288.50	D004462	1.50	<0.005		0.001
			288.50	290.00	D004463	1.50	<0.005		0.001
			290.00	291.50	D004464	1.50	<0.005		0.001
			291.50	293.00	D004465	1.50	<0.005		0.001
			293.00	294.50	D004466	1.50	0.015		0.015
			294.50	296.00	D004467	1.50	0.065		0.065
			296.00	297.50	D004469	1.50	<0.005		0.001
			297.50	299.00	D004470	1.50	0.035		0.035
			299.00	300.50	D004471	1.50	0.027		0.027
			300.50	302.00	D004472	1.50	<0.005		0.001
			302.00	303.50	D004473	1.50	<0.005		0.001
			303.50	305.00	D004474	1.50	<0.005		0.001
			305.00	306.50	D004475	1.50	0.007		0.007
			306.50	308.00	D004476	1.50	0.007		0.007
			308.00	309.50	D004477	1.50	0.046		0.046
			309.50	311.00	D004479	1.50	<0.005		0.001
272.00	287.00	SY; POR <b>Syénite; Porphyrique</b> induré, phénocristaux ± 0.2-1 cm, HM++, CL++, calcite, PY fine							
311.00	320.00	SY; POR; MOY <b>Syénite; Porphyrique; Grains moyens</b> phénocristaux de FP automorphe à sub automorphe ± 0.2-1 cm , altération en calcite, hématisation, chloritisation et séricitisation	311.00	312.50	D004480	1.50	<0.005		0.001
			312.50	314.00	D004481	1.50	<0.005		0.001
			314.00	315.50	D004482	1.50	<0.005		0.001
			315.50	317.00	D004483	1.50	0.007		0.007
			317.00	318.50	D004484	1.50	<0.005		0.001
			318.50	320.00	D004486	1.50	<0.005		0.001
			320.00	321.50	D004487	1.50	<0.005		0.001
			321.50	323.00	D004489	1.50	<0.005		0.001
			323.00	324.50	D004490	1.50	<0.005		0.001
324.50	356.00	SY; POR; MOY <b>Syénite; Porphyrique; Grains moyens</b> phénocristaux de FP automorphe à sub automorphe ± 0.3-3 cm, BO++, CL+, SR+, HM+++, calcite	324.50	326.00	D004491	1.50	<0.005		0.001
			326.00	327.50	D004492	1.50	<0.005		0.001
			327.50	329.00	D004493	1.50	<0.005		0.001
			329.00	330.50	D004494	1.50	<0.005		0.001
			330.50	332.00	D004495	1.50	<0.005		0.001
			332.00	333.50	D004496	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	333.50	335.00	D004497	1.50	<0.005		0.001
	335.00	336.50	D004499	1.50	<0.005		0.001
	336.50	338.00	D004500	1.50	<0.005		0.001
	338.00	339.50	D004501	1.50	<0.005		0.001
	339.50	341.00	D004502	1.50	<0.005		0.001
	341.00	342.50	D004503	1.50	<0.005		0.001
	342.50	344.00	D004504	1.50	<0.005		0.001
	344.00	345.50	D004505	1.50	<0.005		0.001
	345.50	347.00	D004506	1.50	<0.005		0.001
	347.00	348.50	D004507	1.50	<0.005		0.001
	348.50	350.00	D004509	1.50	<0.005		0.001
	350.00	351.50	D004510	1.50	0.006		0.006
	351.50	353.00	D004511	1.50	<0.005		0.001
	353.00	354.50	D004512	1.50	<0.005		0.001
	354.50	356.00	D004513	1.50	<0.005		0.001
	356.00	357.50	D004514	1.50	<0.005		0.001
	357.50	359.00	D004515	1.50	<0.005		0.001
	359.00	360.50	D004516	1.50	0.034		0.034
	360.50	362.00	D004517	1.50	<0.005		0.001
	362.00	363.50	D004519	1.50	<0.005		0.001
	363.50	365.00	D004520	1.50	<0.005		0.001
	365.00	366.50	D004521	1.50	<0.005		0.001
	366.50	368.00	D004522	1.50	<0.005		0.001
	368.00	369.50	D004523	1.50	<0.005		0.001
	369.50	371.00	D004524	1.50	<0.005		0.001
	371.00	372.50	D004526	1.50	<0.005		0.001
	372.50	374.00	D004527	1.50	0.078		0.078
	374.00	375.50	D004529	1.50	0.005		0.005
	375.50	377.00	D004530	1.50	<0.005		0.001
	377.00	378.50	D004531	1.50	<0.005		0.001
	378.50	380.00	D004532	1.50	0.005		0.005
	380.00	381.50	D004533	1.50	0.047		0.047
	381.50	383.00	D004534	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
383.00    438.00 SY; POR; MOY <b>Syénite; Porphyrique; Grains moyens</b> phénocristaux de FP automorphe à sub arrondi, calcite, chlorite, hématite, PY fine	383.00	384.50	D004535	1.50	0.013		0.013	
	384.50	386.00	D004536	1.50	<0.005		0.001	
	386.00	387.50	D004537	1.50	<0.005		0.001	
	387.50	389.00	D004539	1.50	<0.005		0.001	
	389.00	390.50	D004540	1.50	<0.005		0.001	
	390.50	392.00	D004541	1.50	<0.005		0.001	
	392.00	393.50	D004542	1.50	0.007		0.007	
	393.50	395.00	D004543	1.50	0.031		0.031	
	395.00	396.50	D004544	1.50	0.008		0.008	
	396.50	398.00	D004545	1.50	<0.005		0.001	
	398.00	399.50	D004546	1.50	0.006		0.006	
	399.50	401.00	D004547	1.50	<0.005		0.001	
	401.00	402.50	D004549	1.50	0.135		0.135	
	402.50	404.00	D004550	1.50	<0.005		0.001	
	404.00	405.50	D004551	1.50	<0.005		0.001	
	405.50	407.00	D004552	1.50	<0.005		0.001	
	407.00	408.50	D004553	1.50	<0.005		0.001	
	408.50	410.00	D004554	1.50	<0.005		0.001	
	410.00	411.50	D004555	1.50	<0.005		0.001	
	411.50	413.00	D004556	1.50	<0.005		0.001	
	413.00	414.50	D004557	1.50	0.006		0.006	
	414.50	416.00	D004559	1.50	<0.005		0.001	
	416.00	417.50	D004560	1.50	<0.005		0.001	
	417.50	419.00	D004561	1.50	<0.005		0.001	
	419.00	420.50	D004562	1.50	<0.005		0.001	
	420.50	422.00	D004563	1.50	<0.005		0.001	
	422.00	423.50	D004564	1.50	<0.005		0.001	
423.50	425.00	D004566	1.50	<0.005		0.001		
425.00	426.50	D004567	1.50	0.008		0.008		
426.50	428.00	D004569	1.50	0.012		0.012		
428.00	429.50	D004570	1.50	<0.005		0.001		
429.50	431.00	D004571	1.50	0.005		0.005		
431.00	432.50	D004572	1.50	0.007		0.007		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	432.50	434.00	D004573	1.50	<0.005		0.001
	434.00	435.50	D004574	1.50	<0.005		0.001
	435.50	437.00	D004575	1.50	<0.005		0.001
	437.00	438.50	D004576	1.50	0.008		0.008
	438.50	440.00	D004577	1.50	<0.005		0.001
	440.00	441.50	D004579	1.50	<0.005		0.001
	441.50	443.00	D004580	1.50	<0.005		0.001
	443.00	444.50	D004581	1.50	0.017		0.017
	444.50	446.00	D004582	1.50	0.005		0.005
	446.00	447.50	D004583	1.50	<0.005		0.001
	447.50	449.00	D004584	1.50	0.026		0.026
	449.00	450.50	D004585	1.50	0.013		0.013
	450.50	452.00	D004586	1.50	0.014		0.014
	452.00	453.50	D004587	1.50	0.029		0.029
	453.50	455.00	D004589	1.50	0.015		0.015
	455.00	456.50	D004590	1.50	0.027		0.027
	456.50	458.00	D004591	1.50	0.024		0.024
	458.00	459.50	D004592	1.50	0.069		0.069
	459.50	461.00	D004593	1.50	0.056		0.056
	461.00	462.50	D004594	1.50	0.043		0.043
	462.50	464.00	D004595	1.50	0.072		0.072
	464.00	465.50	D004596	1.50	0.119		0.119
	465.50	467.00	D004597	1.50	0.078		0.078
467.00	Fin du sondage Nombre d'échantillons : 307 Nombre d'échantillons QAQC : 43 Longueur totale échantillonnée : 459.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
18.50	20.00	D004258	D004257	1.50	0.194	0.194
32.00	32.00	D004268	J	0.00	0.706	0.706
45.50	47.00	D004278	D004277	1.50	0.005	0.005
54.50	54.50	D004285	M1	0.00	<0.005	0.001
57.50	57.50	D004288	K	0.00	1.115	1.115
71.00	72.50	D004298	D004297	1.50	0.175	0.175
84.50	84.50	D004308	L	0.00	2.140	2.140
98.00	99.50	D004318	D004317	1.50	0.076	0.076
107.00	107.00	D004325	M1	0.00	<0.005	0.001
110.00	110.00	D004328	M	0.00	3.000	3.000
123.50	125.00	D004338	D004337	1.50	0.037	0.037
137.50	137.50	D004348	J	0.00	0.792	0.792
151.00	152.50	D004358	D004357	1.50	0.469	0.469
160.00	160.00	D004365	M1	0.00	<0.005	0.001
162.50	162.50	D004368	K	0.00	0.971	0.971
176.00	177.50	D004378	D004377	1.50	0.868	0.868
189.50	189.50	D004388	L	0.00	2.280	2.280
203.00	204.50	D004398	D004397	1.50	<0.005	0.001
212.00	212.00	D004405	M1	0.00	<0.005	0.001
215.00	215.00	D004408	M	0.00	3.020	3.020
228.50	230.00	D004418	D004417	1.50	0.010	0.010
242.00	242.00	D004428	J	0.00	0.829	0.829
255.50	256.60	D004438	D004437	1.10	<0.005	0.001
264.00	264.00	D004445	M1	0.00	<0.005	0.001
267.00	267.00	D004448	K	0.00	1.115	1.115
281.00	282.50	D004458	D004457	1.50	<0.005	0.001
294.50	294.50	D004468	L	0.00	2.300	2.300
308.00	309.50	D004478	D004477	1.50	0.045	0.045
317.00	317.00	D004485	M1	0.00	<0.005	0.001
320.00	320.00	D004488	K	0.00	0.995	0.995
333.50	335.00	D004498	D004497	1.50	<0.005	0.001
347.00	347.00	D004508	L	0.00	2.190	2.190
360.50	362.00	D004518	D004517	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
369.50	369.50	D004525	M1	0.00	<0.005	0.001
372.50	372.50	D004528	M	0.00	3.000	3.000
386.00	387.50	D004538	D004537	1.50	<0.005	0.001
399.50	399.50	D004548	J	0.00	0.719	0.719
413.00	414.50	D004558	D004557	1.50	<0.005	0.001
422.00	422.00	D004565	M1	0.00	<0.005	0.001
425.00	425.00	D004568	K	0.00	1.030	1.030
438.50	440.00	D004578	D004577	1.50	<0.005	0.001
452.00	452.00	D004588	L	0.00	2.150	2.150
465.50	467.00	D004598	D004597	1.50	0.054	0.054



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-182**

Titre minier :

Section :                      630500

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-05-13

Date de description :

Au :                      2010-05-27

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -67.00°  
 Longueur :                      435.00 m

Est	630 499.6
Nord	5 374 199.3
Élévation	307.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.10°	-72.90°	Oui
Reflex	6.00	1.20°	-73.10°	Oui
Reflex	9.00	1.20°	-73.00°	Oui
Reflex	12.00	9.50°	-73.10°	Non
Reflex	15.00	8.90°	-72.90°	Non
Reflex	18.00	9.40°	-73.00°	Non
Reflex	21.00	8.40°	-72.90°	Non
Reflex	24.00	8.70°	-72.90°	Non
Reflex	27.00	9.00°	-73.00°	Non
Reflex	30.00	8.80°	-73.00°	Non
Reflex	33.00	8.40°	-72.90°	Non
Reflex	36.00	8.50°	-72.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	7.90°	-72.90°	Non
Reflex	42.00	8.50°	-72.90°	Non
Reflex	45.00	9.50°	-72.90°	Non
Reflex	48.00	9.90°	-73.00°	Non
Reflex	51.00	10.40°	-73.00°	Non
Reflex	54.00	10.30°	-72.90°	Non
Reflex	57.00	10.00°	-73.00°	Non
Reflex	60.00	10.10°	-73.00°	Non
Reflex	63.00	9.60°	-73.00°	Non
Reflex	66.00	10.10°	-73.10°	Non
Reflex	69.00	10.00°	-73.00°	Non
Reflex	72.00	10.20°	-73.00°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	10.60°	-73.10°	Non
Reflex	78.00	11.60°	-73.10°	Non
Reflex	81.00	11.30°	-73.00°	Non
Reflex	84.00	11.20°	-73.00°	Non
Reflex	87.00	10.20°	-73.00°	Non
Reflex	90.00	10.90°	-73.10°	Non
Reflex	93.00	12.10°	-73.10°	Oui
Reflex	96.00	11.70°	-73.00°	Non
Reflex	99.00	10.40°	-73.00°	Non
Reflex	102.00	10.00°	-73.00°	Non
Reflex	105.00	12.20°	-73.00°	Oui
Reflex	108.00	10.90°	-72.90°	Non
Reflex	111.00	11.00°	-72.90°	Non
Reflex	114.00	11.00°	-72.90°	Non
Reflex	117.00	10.90°	-73.00°	Non
Reflex	120.00	11.70°	-72.90°	Non
Reflex	123.00	10.90°	-72.90°	Non
Reflex	126.00	11.80°	-73.00°	Non
Reflex	129.00	11.90°	-73.00°	Non
Reflex	132.00	10.40°	-72.90°	Non
Reflex	135.00	11.70°	-72.90°	Non
Reflex	138.00	8.90°	-73.00°	Oui
Reflex	141.00	11.20°	-73.00°	Non
Reflex	144.00	12.90°	-73.00°	Non
Reflex	147.00	11.40°	-73.00°	Non
Reflex	150.00	12.00°	-73.10°	Non
Reflex	153.00	12.20°	-73.10°	Non
Reflex	156.00	12.20°	-73.10°	Non
Reflex	159.00	12.90°	-73.10°	Non
Reflex	162.00	11.90°	-73.10°	Non
Reflex	165.00	13.10°	-73.00°	Oui
Reflex	168.00	11.40°	-73.10°	Non
Reflex	171.00	12.30°	-73.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	174.00	13.10°	-73.20°	Non
Reflex	177.00	13.50°	-73.10°	Non
Reflex	180.00	12.30°	-73.10°	Non
Reflex	183.00	13.40°	-73.20°	Non
Reflex	186.00	13.30°	-73.10°	Non
Reflex	189.00	12.20°	-73.10°	Non
Reflex	192.00	12.40°	-73.10°	Non
Reflex	195.00	10.30°	-73.00°	Oui
Reflex	198.00	12.40°	-73.10°	Non
Reflex	201.00	13.30°	-73.10°	Non
Reflex	204.00	13.20°	-73.20°	Non
Reflex	207.00	11.80°	-73.00°	Non
Reflex	210.00	12.70°	-73.00°	Non
Reflex	213.00	11.40°	-73.00°	Non
Reflex	216.00	11.40°	-73.10°	Non
Reflex	219.00	11.70°	-73.10°	Non
Reflex	222.00	12.70°	-73.10°	Non
Reflex	225.00	12.40°	-73.10°	Non
Reflex	228.00	12.30°	-73.10°	Non
Reflex	231.00	11.60°	-73.20°	Non
Reflex	234.00	12.00°	-73.10°	Non
Reflex	237.00	11.20°	-73.10°	Non
Reflex	240.00	12.20°	-73.20°	Non
Reflex	243.00	12.60°	-73.20°	Non
Reflex	246.00	13.70°	-73.20°	Oui
Reflex	249.00	12.80°	-73.20°	Non
Reflex	252.00	12.10°	-73.10°	Non
Reflex	255.00	14.20°	-73.20°	Non
Reflex	258.00	12.30°	-73.10°	Non
Reflex	261.00	14.20°	-73.20°	Non
Reflex	264.00	12.50°	-73.20°	Non
Reflex	267.00	14.30°	-73.20°	Oui
Reflex	270.00	12.60°	-73.10°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	13.70°	-73.20°	Non	Reflex	372.00	15.90°	-73.40°	Non
Reflex	276.00	13.80°	-73.20°	Non	Reflex	375.00	14.70°	-73.30°	Non
Reflex	279.00	13.80°	-73.20°	Non	Reflex	378.00	13.50°	-73.30°	Oui
Reflex	282.00	12.90°	-73.20°	Non	Reflex	381.00	15.40°	-73.40°	Non
Reflex	285.00	12.90°	-73.20°	Non	Reflex	384.00	15.50°	-73.30°	Non
Reflex	288.00	13.80°	-73.30°	Non	Reflex	387.00	15.20°	-73.30°	Non
Reflex	291.00	12.40°	-73.20°	Non	Reflex	390.00	15.00°	-73.40°	Non
Reflex	294.00	14.10°	-73.20°	Oui	Reflex	393.00	15.80°	-73.30°	Non
Reflex	297.00	13.50°	-73.20°	Non	Reflex	396.00	16.30°	-73.50°	Oui
Reflex	300.00	14.00°	-73.30°	Non	Reflex	399.00	15.00°	-73.30°	Non
Reflex	303.00	13.90°	-73.20°	Non	Reflex	402.00	16.20°	-73.40°	Non
Reflex	306.00	13.80°	-73.30°	Non	Reflex	405.00	16.40°	-73.50°	Non
Reflex	309.00	13.90°	-73.30°	Non	Reflex	408.00	17.40°	-73.50°	Non
Reflex	312.00	15.10°	-73.30°	Non	Reflex	411.00	15.60°	-73.40°	Non
Reflex	315.00	15.30°	-73.20°	Non	Reflex	414.00	15.00°	-73.40°	Non
Reflex	318.00	15.70°	-73.30°	Non	Reflex	417.00	14.40°	-73.30°	Non
Reflex	321.00	15.30°	-73.30°	Non	Reflex	420.00	14.80°	-73.40°	Non
Reflex	324.00	14.30°	-73.30°	Non	Reflex	423.00	14.30°	-73.40°	Non
Reflex	327.00	14.30°	-73.30°	Non	Reflex	426.00	15.00°	-73.40°	Non
Reflex	330.00	14.90°	-73.40°	Non	Reflex	429.00	15.90°	-73.40°	Non
Reflex	333.00	15.50°	-73.30°	Non	Reflex	432.00	15.80°	-73.40°	Non
Reflex	336.00	15.00°	-73.30°	Non	Reflex	435.00	16.50°	-73.40°	Non
Reflex	339.00	15.00°	-73.30°	Non					
Reflex	342.00	15.40°	-73.30°	Non					
Reflex	345.00	14.80°	-73.30°	Non					
Reflex	348.00	16.30°	-73.40°	Oui					
Reflex	351.00	14.70°	-73.30°	Non					
Reflex	354.00	14.10°	-73.30°	Non					
Reflex	357.00	14.80°	-73.30°	Non					
Reflex	360.00	14.30°	-73.30°	Non					
Reflex	363.00	14.40°	-73.40°	Non					
Reflex	366.00	14.20°	-73.30°	Non					
Reflex	369.00	15.00°	-73.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	7.00	MT <b>Mort-terrain</b>						
7.00	23.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains,porphyrique avec phénocristaux Xmm.	7.00	8.50	D017731	1.50	0.048	0.048
			8.50	10.00	D017732	1.50	0.015	0.015
			10.00	11.50	D017733	1.50	0.344	0.344
			11.50	13.00	D017734	1.50	0.420	0.420
			13.00	14.50	D017735	1.50	0.974	0.974
			14.50	16.00	D017736	1.50	0.940	0.940
			16.00	17.50	D017738	1.50	0.429	0.429
17.50	36.00	FRC <b>Fracturé</b> Zone fracturé avec de carotes perdues.	17.50	19.00	D017739	1.50	0.817	0.817
			19.00	20.50	D017740	1.50	2.170	2.170
			20.50	22.00	D017741	1.50	2.730	2.730
			22.00	23.00	D017742	1.00	0.132	0.132
23.00	24.00	NR <b>Carotte perdue</b>						
24.00	28.50	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains fins, porphyrique avec de phénocristaux Xmm.	24.00	25.50	D017743	1.50	0.409	0.409
			25.50	27.00	D017744	1.50	0.183	0.183
			27.00	28.50	D017745	1.50	0.109	0.109
28.50	29.10	NR <b>Carotte perdue</b>						
29.10	32.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite à grains fins avec passage porphyrique de phénocristaux Xmm.	29.10	30.50	D017746	1.40	0.110	0.110
			30.50	32.00	D017748	1.50	0.149	0.149
32.00	33.00	NR <b>Carotte perdue</b>						
33.00	435.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains fins, porphyrique différenciellement avec phénocristaux Xmm.	33.00	34.50	D017749	1.50	0.014	0.014
			34.50	35.80	D017750	1.30	0.091	0.091
			35.80	37.00	D017751	1.20	1.860	1.860
			37.00	38.50	D017752	1.50	0.254	0.254
			38.50	40.00	D017753	1.50	0.488	0.488
			40.00	41.50	D017754	1.50	0.680	0.680
			41.50	43.00	D017755	1.50	0.201	0.201
			43.00	44.50	D017756	1.50	0.530	0.530
			44.50	46.00	D017758	1.50	0.056	0.056

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	46.00	47.50	D017759	1.50	0.037		0.037
	47.50	49.00	D017760	1.50	0.029		0.029
	49.00	50.50	D017761	1.50	0.007		0.007
	50.50	52.00	D017763	1.50	<0.005		0.001
	52.00	53.50	D017764	1.50	0.037		0.037
	53.50	55.00	D017765	1.50	<0.005		0.001
	55.00	56.50	D017766	1.50	<0.005		0.001
	56.50	58.00	D017768	1.50	<0.005		0.001
	58.00	59.50	D017769	1.50	0.005		0.005
	59.50	61.00	D017770	1.50	0.190		0.190
	61.00	62.50	D017771	1.50	0.007		0.007
	62.50	64.00	D017772	1.50	0.039		0.039
	64.00	65.50	D017773	1.50	0.154		0.154
	65.50	67.00	D017774	1.50	0.308		0.308
	67.00	68.50	D017775	1.50	0.272		0.272
	68.50	70.00	D017776	1.50	1.195		1.195
	70.00	71.50	D017778	1.50	1.010		1.010
	71.50	73.00	D017779	1.50	0.623		0.623
	73.00	74.50	D017780	1.50	0.335		0.335
	74.50	76.00	D017781	1.50	0.138		0.138
	76.00	77.50	D017782	1.50	0.192		0.192
	77.50	79.00	D017783	1.50	0.123		0.123
	79.00	80.50	D017784	1.50	0.100		0.100
	80.50	82.00	D017785	1.50	0.209		0.209
	82.00	83.50	D017786	1.50	0.021		0.021
	83.50	85.00	D017788	1.50	0.080		0.080
	85.00	86.50	D017789	1.50	0.105		0.105
	86.50	88.00	D017790	1.50	0.135		0.135
	88.00	89.50	D017791	1.50	0.110		0.110
	89.50	91.00	D017792	1.50	0.162		0.162
	91.00	92.50	D017793	1.50	0.087		0.087
	92.50	94.00	D017794	1.50	0.132		0.132
	94.00	95.50	D017795	1.50	0.202		0.202

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	95.50	97.00	D017796	1.50	0.147		0.147
	97.00	98.50	D017798	1.50	0.286		0.286
	98.50	100.00	D017799	1.50	0.042		0.042
	100.00	101.50	D017800	1.50	0.035		0.035
	101.50	103.00	D017801	1.50	0.043		0.043
	103.00	104.50	D017803	1.50	0.010		0.010
	104.50	106.00	D017804	1.50	0.033		0.033
	106.00	107.50	D017805	1.50	0.050		0.050
	107.50	109.00	D017806	1.50	0.092		0.092
	109.00	110.50	D017808	1.50	0.020		0.020
	110.50	112.00	D017809	1.50	0.091		0.091
	112.00	113.50	D017810	1.50	0.025		0.025
	113.50	115.00	D017811	1.50	<0.005		0.001
	115.00	116.50	D017812	1.50	0.012		0.012
	116.50	118.00	D017813	1.50	0.017		0.017
	118.00	119.50	D017814	1.50	0.008		0.008
	119.50	121.00	D017815	1.50	<0.005		0.001
	121.00	122.50	D017816	1.50	<0.005		0.001
	122.50	124.00	D017818	1.50	<0.005		0.001
	124.00	125.50	D017819	1.50	0.009		0.009
	125.50	127.00	D017820	1.50	<0.005		0.001
	127.00	128.50	D017821	1.50	0.023		0.023
	128.50	130.00	D017822	1.50	0.060		0.060
	130.00	131.50	D017823	1.50	0.013		0.013
	131.50	133.00	D017824	1.50	0.065		0.065
	133.00	134.50	D017825	1.50	0.641		0.641
	134.50	136.00	D017826	1.50	0.060		0.060
	136.00	137.50	D017828	1.50	0.060		0.060
	137.50	139.00	D017829	1.50	0.008		0.008
	139.00	140.50	D017830	1.50	0.118		0.118
	140.50	142.00	D017831	1.50	0.745		0.745
	142.00	143.50	D017832	1.50	0.159		0.159
	143.50	145.00	D017833	1.50	0.160		0.160

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	145.00	146.50	D017834	1.50	0.382		0.382
	146.50	148.00	D017835	1.50	0.169		0.169
	148.00	149.50	D017836	1.50	0.303		0.303
	149.50	151.00	D017838	1.50	0.013		0.013
	151.00	152.50	D017839	1.50	0.043		0.043
	152.50	154.00	D017840	1.50	0.039		0.039
	154.00	155.50	D017841	1.50	0.024		0.024
	155.50	157.00	D017843	1.50	0.014		0.014
	157.00	158.50	D017844	1.50	0.017		0.017
	158.50	160.00	D017845	1.50	0.031		0.031
	160.00	161.50	D017846	1.50	0.024		0.024
	161.50	163.00	D017848	1.50	0.127		0.127
	163.00	164.50	D017849	1.50	0.028		0.028
	164.50	166.00	D017850	1.50	0.367		0.367
	166.00	167.50	D017851	1.50	0.712		0.712
	167.50	169.00	D017852	1.50	0.011		0.011
	169.00	170.50	D017853	1.50	0.338		0.338
	170.50	172.00	D017854	1.50	0.203		0.203
	172.00	173.50	D017855	1.50	0.202		0.202
	173.50	175.00	D017856	1.50	0.206		0.206
	175.00	176.50	D017858	1.50	0.496		0.496
	176.50	178.00	D017859	1.50	0.010		0.010
	178.00	179.50	D017860	1.50	0.005		0.005
	179.50	181.00	D017861	1.50	<0.005		0.001
	181.00	182.50	D017862	1.50	<0.005		0.001
	182.50	184.00	D017863	1.50	<0.005		0.001
	184.00	185.50	D017864	1.50	<0.005		0.001
	185.50	187.00	D017865	1.50	<0.005		0.001
	187.00	188.50	D017866	1.50	<0.005		0.001
	188.50	190.00	D017868	1.50	0.005		0.005
	190.00	191.50	D017869	1.50	0.029		0.029
	191.50	193.00	D017870	1.50	<0.005		0.001
	193.00	194.50	D017871	1.50	0.097		0.097

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	194.50	196.00	D017872	1.50	<0.005		0.001
	196.00	197.50	D017873	1.50	0.111		0.111
	197.50	199.00	D017874	1.50	0.084		0.084
	199.00	200.50	D017875	1.50	0.365		0.365
	200.50	202.00	D017876	1.50	1.310		1.310
	202.00	203.50	D017878	1.50	0.050		0.050
	203.50	205.00	D017879	1.50	0.050		0.050
	205.00	206.50	D017880	1.50	<0.005		0.001
	206.50	208.00	D017881	1.50	<0.005		0.001
	208.00	209.50	D017883	1.50	<0.005		0.001
	209.50	211.00	D017884	1.50	0.033		0.033
	211.00	212.50	D017885	1.50	0.076		0.076
	212.50	214.00	D017886	1.50	0.213		0.213
	214.00	215.50	D017888	1.50	0.113		0.113
	215.50	217.00	D017889	1.50	0.427		0.427
	217.00	218.50	D017890	1.50	0.436		0.436
	218.50	220.00	D017891	1.50	0.255		0.255
	220.00	221.50	D017892	1.50	0.006		0.006
	221.50	223.00	D017893	1.50	<0.005		0.001
	223.00	224.50	D017894	1.50	<0.005		0.001
	224.50	226.00	D017895	1.50	<0.005		0.001
	226.00	227.50	D017896	1.50	<0.005		0.001
	227.50	229.00	D017898	1.50	<0.005		0.001
	229.00	230.50	D017899	1.50	<0.005		0.001
	230.50	232.00	D017900	1.50	<0.005		0.001
	232.00	233.50	D017901	1.50	<0.005		0.001
	233.50	235.00	D017902	1.50	<0.005		0.001
	235.00	236.50	D017903	1.50	<0.005		0.001
	236.50	238.00	D017904	1.50	<0.005		0.001
	238.00	239.50	D017905	1.50	<0.005		0.001
	239.50	241.00	D017906	1.50	<0.005		0.001
	241.00	242.50	D017908	1.50	0.006		0.006
	242.50	244.00	D017909	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	244.00	245.50	D017910	1.50	<0.005		0.001
	245.50	247.00	D017911	1.50	0.025		0.025
	247.00	248.50	D017912	1.50	0.251		0.251
	248.50	250.00	D017913	1.50	0.036		0.036
	250.00	251.50	D017914	1.50	<0.005		0.001
	251.50	253.00	D017915	1.50	0.013		0.013
	253.00	254.50	D017916	1.50	0.013		0.013
	254.50	256.00	D017918	1.50	0.013		0.013
	256.00	257.50	D017919	1.50	<0.005		0.001
	257.50	259.00	D017920	1.50	<0.005		0.001
	259.00	260.50	D017921	1.50	<0.005		0.001
	260.50	262.00	D017923	1.50	<0.005		0.001
	262.00	263.50	D017924	1.50	<0.005		0.001
	263.50	265.00	D017925	1.50	<0.005		0.001
	265.00	266.50	D017926	1.50	<0.005		0.001
	266.50	268.00	D017928	1.50	<0.005		0.001
	268.00	269.50	D017929	1.50	<0.005		0.001
	269.50	271.00	D017930	1.50	0.011		0.011
	271.00	272.50	D017931	1.50	<0.005		0.001
	272.50	274.00	D017932	1.50	<0.005		0.001
	274.00	275.50	D017933	1.50	0.006		0.006
	275.50	277.00	D017934	1.50	<0.005		0.001
	277.00	278.50	D017935	1.50	<0.005		0.001
	278.50	280.00	D017936	1.50	<0.005		0.001
	280.00	281.50	D017938	1.50	0.005		0.005
	281.50	283.00	D017939	1.50	<0.005		0.001
	283.00	284.50	D017940	1.50	<0.005		0.001
	284.50	286.00	D017941	1.50	<0.005		0.001
	286.00	287.50	D017942	1.50	<0.005		0.001
	287.50	289.00	D017943	1.50	0.006		0.006
	289.00	290.50	D017944	1.50	<0.005		0.001
	290.50	292.00	D017945	1.50	<0.005		0.001
	292.00	293.50	D017946	1.50	0.012		0.012

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	293.50	295.00	D017948	1.50	0.006		0.006
	295.00	296.50	D017949	1.50	<0.005		0.001
	296.50	298.00	D017950	1.50	<0.005		0.001
	298.00	299.50	D017951	1.50	<0.005		0.001
	299.50	301.00	D017952	1.50	0.009		0.009
	301.00	302.50	D017953	1.50	<0.005		0.001
	302.50	304.00	D017954	1.50	<0.005		0.001
	304.00	305.50	D017955	1.50	<0.005		0.001
	305.50	307.00	D017956	1.50	<0.005		0.001
	307.00	308.50	D017958	1.50	0.028		0.028
	308.50	310.00	D017959	1.50	<0.005		0.001
	310.00	311.50	D017960	1.50	<0.005		0.001
	311.50	313.00	D017961	1.50	<0.005		0.001
	313.00	314.50	D017963	1.50	0.050		0.050
	314.50	316.00	D017964	1.50	0.005		0.005
	316.00	317.50	D017965	1.50	<0.005		0.001
	317.50	319.00	D017966	1.50	<0.005		0.001
	319.00	320.50	D017968	1.50	<0.005		0.001
	320.50	322.00	D017969	1.50	<0.005		0.001
	322.00	323.50	D017970	1.50	<0.005		0.001
	323.50	325.00	D017971	1.50	<0.005		0.001
	325.00	326.50	D017972	1.50	<0.005		0.001
	326.50	328.00	D017973	1.50	0.005		0.005
	328.00	329.50	D017974	1.50	0.006		0.006
	329.50	331.00	D017975	1.50	0.025		0.025
	331.00	332.50	D017976	1.50	<0.005		0.001
	332.50	334.00	D017978	1.50	<0.005		0.001
	334.00	335.50	D017979	1.50	<0.005		0.001
	335.50	337.00	D017980	1.50	0.121		0.121
	337.00	338.50	D017981	1.50	0.030		0.030
	338.50	340.00	D017982	1.50	0.006		0.006
	340.00	341.50	D017983	1.50	<0.005		0.001
	341.50	343.00	D017984	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	343.00	344.50	D017985	1.50	<0.005		0.001
	344.50	346.00	D017986	1.50	<0.005		0.001
	346.00	347.50	D017988	1.50	0.005		0.005
	347.50	349.00	D017989	1.50	<0.005		0.001
	349.00	350.50	D017990	1.50	<0.005		0.001
	350.50	352.00	D017991	1.50	<0.005		0.001
	352.00	353.50	D017992	1.50	0.077		0.077
	353.50	355.00	D017993	1.50	0.020		0.020
	355.00	356.50	D017994	1.50	0.017		0.017
	356.50	358.00	D017995	1.50	0.186		0.186
	358.00	359.50	D017996	1.50	0.031		0.031
	359.50	361.00	D017998	1.50	0.007		0.007
	361.00	362.50	D017999	1.50	0.066		0.066
	362.50	364.00	D018000	1.50	0.313		0.313
	364.00	365.50	D018001	1.50	0.106		0.106
	365.50	367.00	D018003	1.50	0.348		0.348
	367.00	368.50	D018004	1.50	<0.005		0.001
	368.50	370.00	D018005	1.50	0.005		0.005
	370.00	371.50	D018006	1.50	<0.005		0.001
	371.50	373.00	D018008	1.50	<0.005		0.001
	373.00	374.50	D018009	1.50	<0.005		0.001
	374.50	376.00	D018010	1.50	<0.005		0.001
	376.00	377.50	D018011	1.50	<0.005		0.001
	377.50	379.00	D018012	1.50	<0.005		0.001
	379.00	380.50	D018013	1.50	<0.005		0.001
	380.50	382.00	D018014	1.50	<0.005		0.001
	382.00	383.50	D018015	1.50	0.006		0.006
	383.50	385.00	D018016	1.50	0.007		0.007
	385.00	386.50	D018018	1.50	0.649		0.649
	386.50	388.00	D018019	1.50	0.137		0.137
	388.00	389.50	D018020	1.50	0.116		0.116
	389.50	391.00	D018021	1.50	0.008		0.008
	391.00	392.50	D018022	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	392.50	394.00	D018023	1.50	<0.005		0.001
	394.00	395.50	D018024	1.50	<0.005		0.001
	395.50	397.00	D018025	1.50	<0.005		0.001
	397.00	398.50	D018026	1.50	<0.005		0.001
	398.50	400.00	D018028	1.50	0.005		0.005
	400.00	401.50	D018029	1.50	<0.005		0.001
	401.50	403.00	D018030	1.50	<0.005		0.001
	403.00	404.50	D018031	1.50	<0.005		0.001
	404.50	406.00	D018032	1.50	0.013		0.013
	406.00	407.50	D018033	1.50	0.005		0.005
	407.50	409.00	D018034	1.50	0.020		0.020
	409.00	410.50	D018035	1.50	0.038		0.038
	410.50	412.00	D018036	1.50	<0.005		0.001
	412.00	413.50	D018038	1.50	1.070		1.070
	413.50	415.00	D018039	1.50	0.294		0.294
	415.00	416.50	D018040	1.50	0.181		0.181
	416.50	418.00	D018041	1.50	0.181		0.181
	418.00	419.50	D018043	1.50	0.036		0.036
	419.50	421.00	D018044	1.50	<0.005		0.001
	421.00	422.50	D018045	1.50	0.037		0.037
	422.50	424.00	D018046	1.50	0.362		0.362
	424.00	425.50	D018048	1.50	0.030		0.030
	425.50	427.00	D018049	1.50	0.422		0.422
	427.00	428.50	D018050	1.50	0.013		0.013
	428.50	430.00	D018051	1.50	0.005		0.005
	430.00	431.50	D018052	1.50	<0.005		0.001
	431.50	433.00	D018053	1.50	<0.005		0.001
	433.00	434.00	D018054	1.00	<0.005		0.001
	434.00	435.00	D018055	1.00	0.005		0.005
435.00	Fin du sondage Nombre d'échantillons : 285 Nombre d'échantillons QAQC : 40 Longueur totale échantillonnée : 425.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	16.00	D017737	D017736	1.50	0.961	0.961
29.10	30.50	D017747	K	1.40	1.025	1.025
43.00	44.50	D017757	D017756	1.50	0.512	0.512
49.00	50.50	D017762	M1	1.50	<0.005	0.001
55.00	56.50	D017767	L	1.50	2.280	2.280
68.50	70.00	D017777	D017776	1.50	1.245	1.245
82.00	83.50	D017787	M	1.50	3.040	3.040
95.50	97.00	D017797	D017796	1.50	0.125	0.125
101.50	103.00	D017802	M1	1.50	<0.005	0.001
107.50	109.00	D017807	J	1.50	0.794	0.794
121.00	122.50	D017817	D017816	1.50	<0.005	0.001
134.50	136.00	D017827	K	1.50	0.972	0.972
148.00	149.50	D017837	D017836	1.50	0.300	0.300
154.00	155.50	D017842	M1	1.50	<0.005	0.001
160.00	161.50	D017847	L	1.50	2.180	2.180
173.50	175.00	D017857	D017856	1.50	0.245	0.245
187.00	188.50	D017867	M	1.50	3.000	3.000
200.50	202.00	D017877	D017876	1.50	1.280	1.280
206.50	208.00	D017882	M1	1.50	<0.005	0.001
212.50	214.00	D017887	J	1.50	0.764	0.764
226.00	227.50	D017897	D017896	1.50	<0.005	0.001
239.50	241.00	D017907	K	1.50	1.020	1.020
253.00	254.50	D017917	D017916	1.50	0.012	0.012
259.00	260.50	D017922	M1	1.50	<0.005	0.001
265.00	266.50	D017927	L	1.50	2.090	2.090
278.50	280.00	D017937	D017936	1.50	<0.005	0.001
292.00	293.50	D017947	M	1.50	2.340	2.340
305.50	307.00	D017957	D017956	1.50	0.005	0.005
311.50	313.00	D017962	M1	1.50	<0.005	0.001
317.50	319.00	D017967	J	1.50	0.743	0.743
331.00	332.50	D017977	D017976	1.50	<0.005	0.001
344.50	346.00	D017987	K	1.50	1.095	1.095
358.00	359.50	D017997	D017996	1.50	0.025	0.025

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
364.00	365.50	D018002	M1	1.50	<0.005	0.001
370.00	371.50	D018007	L	1.50	2.420	2.420
383.50	385.00	D018017	D018016	1.50	0.008	0.008
397.00	398.50	D018027	M	1.50	3.100	3.100
410.50	412.00	D018037	D018036	1.50	0.006	0.006
416.50	418.00	D018042	M1	1.50	<0.005	0.001
422.50	424.00	D018047	J	1.50	0.706	0.706

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-183</b>	Titre minier :	Section :	630500
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Orbit Garant	Lot :		
Décrit par : D.Tremblay	Du : 2010-05-27	Date de description :	2010-07-23
	Au : 2010-06-04		

Collet

Azimut : 0.00°  
 Plongée : -75.00°  
 Longueur : 411.00 m

UTM

Est	630 499.6
Nord	5 374 199.2
Élévation	307.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	0.50°	-80.40°	Non
Reflex	8.00	0.40°	-80.40°	Non
Reflex	11.00	1.10°	-80.30°	Non
Reflex	14.00	40.90°	-80.40°	Oui
Reflex	17.00	0.80°	-80.40°	Non
Reflex	20.00	0.10°	-80.60°	Non
Reflex	23.00	0.20°	-80.60°	Non
Reflex	26.00	359.60°	-80.80°	Non
Reflex	29.00	359.50°	-80.50°	Non
Reflex	32.00	359.90°	-80.50°	Non
Reflex	35.00	359.10°	-80.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.20°	-80.40°	Non
Reflex	41.00	359.40°	-80.60°	Non
Reflex	44.00	359.60°	-80.40°	Non
Reflex	47.00	359.30°	-80.20°	Non
Reflex	50.00	359.60°	-80.30°	Non
Reflex	53.00	0.20°	-80.50°	Non
Reflex	56.00	359.20°	-80.10°	Non
Reflex	59.00	359.10°	-80.50°	Non
Reflex	62.00	359.90°	-80.60°	Non
Reflex	65.00	359.90°	-80.50°	Non
Reflex	68.00	2.10°	-80.40°	Oui
Reflex	71.00	0.40°	-80.40°	Non

Description

Dimension de la carotte : NQ Cimenté : Non Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.30°	-80.30°	Non	Reflex	173.00	1.30°	-80.50°	Non
Reflex	77.00	1.60°	-80.30°	Non	Reflex	176.00	1.70°	-80.50°	Non
Reflex	80.00	2.10°	-80.40°	Non	Reflex	179.00	1.70°	-80.60°	Non
Reflex	83.00	2.30°	-80.40°	Non	Reflex	182.00	1.80°	-80.50°	Non
Reflex	86.00	1.60°	-80.40°	Non	Reflex	185.00	1.20°	-80.40°	Non
Reflex	89.00	2.20°	-80.40°	Non	Reflex	188.00	2.00°	-80.40°	Non
Reflex	92.00	1.40°	-80.30°	Non	Reflex	191.00	1.70°	-80.40°	Non
Reflex	95.00	3.10°	-80.40°	Oui	Reflex	194.00	2.20°	-80.40°	Oui
Reflex	98.00	1.80°	-80.40°	Non	Reflex	197.00	1.80°	-80.40°	Non
Reflex	101.00	2.60°	-80.30°	Non	Reflex	200.00	1.10°	-80.60°	Non
Reflex	104.00	2.50°	-80.40°	Non	Reflex	203.00	1.90°	-80.50°	Non
Reflex	107.00	2.40°	-80.50°	Non	Reflex	206.00	2.10°	-80.60°	Non
Reflex	110.00	2.40°	-80.40°	Non	Reflex	209.00	1.70°	-80.50°	Non
Reflex	113.00	1.30°	-80.60°	Non	Reflex	212.00	4.40°	-80.70°	Non
Reflex	116.00	3.00°	-80.50°	Oui	Reflex	215.00	1.90°	-80.70°	Non
Reflex	119.00	2.10°	-80.60°	Non	Reflex	218.00	1.00°	-80.50°	Non
Reflex	122.00	1.90°	-80.60°	Non	Reflex	221.00	359.50°	-80.50°	Non
Reflex	125.00	1.60°	-80.60°	Non	Reflex	224.00	0.80°	-80.50°	Non
Reflex	128.00	0.80°	-80.60°	Non	Reflex	227.00	1.30°	-80.70°	Non
Reflex	131.00	1.30°	-80.60°	Non	Reflex	230.00	1.10°	-80.70°	Non
Reflex	134.00	1.70°	-80.60°	Non	Reflex	233.00	1.10°	-80.70°	Non
Reflex	137.00	0.50°	-80.50°	Non	Reflex	236.00	1.60°	-80.80°	Non
Reflex	140.00	2.60°	-80.60°	Non	Reflex	239.00	0.80°	-80.70°	Non
Reflex	143.00	0.30°	-80.50°	Non	Reflex	242.00	2.20°	-80.80°	Non
Reflex	146.00	1.00°	-80.50°	Non	Reflex	245.00	1.60°	-80.70°	Non
Reflex	149.00	2.80°	-80.40°	Non	Reflex	248.00	2.50°	-80.80°	Non
Reflex	152.00	2.70°	-80.60°	Non	Reflex	251.00	0.60°	-80.70°	Non
Reflex	155.00	1.30°	-80.50°	Non	Reflex	254.00	0.60°	-80.40°	Non
Reflex	158.00	2.10°	-80.60°	Non	Reflex	257.00	1.60°	-80.80°	Non
Reflex	161.00	1.30°	-80.60°	Non	Reflex	260.00	0.40°	-80.70°	Non
Reflex	164.00	1.90°	-80.60°	Non	Reflex	263.00	2.20°	-80.70°	Non
Reflex	167.00	1.90°	-80.60°	Non	Reflex	266.00	2.20°	-80.70°	Non
Reflex	170.00	1.70°	-80.60°	Non	Reflex	269.00	1.40°	-80.60°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	0.30°	-80.80°	Non	Reflex	371.00	3.70°	-80.70°	Non
Reflex	275.00	359.80°	-80.80°	Non	Reflex	374.00	3.50°	-80.70°	Non
Reflex	278.00	0.30°	-80.80°	Non	Reflex	377.00	3.60°	-80.70°	Non
Reflex	281.00	359.90°	-80.80°	Non	Reflex	380.00	3.90°	-80.80°	Non
Reflex	284.00	1.10°	-80.70°	Non	Reflex	383.00	3.60°	-80.80°	Non
Reflex	287.00	359.60°	-80.70°	Non	Reflex	386.00	3.50°	-80.90°	Non
Reflex	290.00	1.50°	-80.80°	Non	Reflex	389.00	1.40°	-80.80°	Non
Reflex	293.00	0.30°	-80.70°	Non	Reflex	392.00	4.50°	-80.80°	Oui
Reflex	296.00	360.00°	-80.80°	Non	Reflex	395.00	2.10°	-80.80°	Non
Reflex	299.00	1.20°	-80.80°	Non	Reflex	398.00	1.50°	-80.80°	Non
Reflex	302.00	0.80°	-80.70°	Non	Reflex	401.00	1.90°	-80.80°	Non
Reflex	305.00	0.60°	-80.80°	Non	Reflex	404.00	2.30°	-80.80°	Non
Reflex	308.00	358.90°	-80.60°	Non	Reflex	407.00	1.20°	-80.90°	Non
Reflex	311.00	359.60°	-80.70°	Non	Reflex	410.00	1.30°	-80.90°	Non
Reflex	314.00	359.80°	-80.80°	Non					
Reflex	317.00	358.70°	-80.70°	Non					
Reflex	320.00	359.20°	-80.80°	Non					
Reflex	323.00	359.70°	-80.70°	Non					
Reflex	326.00	0.00°	-80.80°	Non					
Reflex	329.00	0.50°	-80.80°	Non					
Reflex	332.00	0.80°	-80.70°	Non					
Reflex	335.00	0.50°	-80.60°	Non					
Reflex	338.00	0.40°	-80.70°	Non					
Reflex	341.00	1.50°	-80.50°	Non					
Reflex	344.00	2.70°	-80.60°	Non					
Reflex	347.00	1.70°	-80.50°	Non					
Reflex	350.00	2.50°	-80.70°	Non					
Reflex	353.00	2.30°	-80.60°	Non					
Reflex	356.00	2.50°	-80.60°	Non					
Reflex	359.00	3.40°	-80.60°	Non					
Reflex	362.00	3.80°	-80.60°	Non					
Reflex	365.00	3.30°	-80.50°	Non					
Reflex	368.00	3.70°	-80.60°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	7.40	MT						
		<b>Mort-terrain</b>						
7.40	117.00	SY; POR	7.40	9.00	D015650	1.60	0.034	0.034
		<b>Syénite; Porphyrique</b>	9.00	10.50	D015651	1.50	<0.005	0.001
		Syénite porphyrique rose et ocre, massive, dure et assez homogène.	10.50	12.00	D015653	1.50	0.009	0.009
		La quantité de porphyres est variable. Ils se présentent xéno à	12.00	13.50	D015654	1.50	0.211	0.211
		idiomorphes. Certains sont zonés, d'autres avec un poutour ou un	13.50	15.00	D015655	1.50	0.512	0.512
		noyau de chlorite.	15.00	16.50	D015656	1.50	0.637	0.637
		Elle est fracturée et occupée par des veinules de	16.50	18.00	D015657	1.50	1.970	1.970
		quartz-albite-carbonates et chlorite. Ce système est assez dense par	18.00	19.50	D015658	1.50	0.910	0.910
		endroits. Elles sont disposées entre	19.50	21.00	D015659	1.50	0.642	0.642
		20°-80°ac et ne dépassent rarement 1cm en épaisseur.	21.00	22.50	D015660	1.50	0.261	0.261
			22.50	24.00	D015661	1.50	0.895	0.895
			24.00	25.50	D015663	1.50	1.520	1.520
			25.50	27.00	D015664	1.50	0.362	0.362
			27.00	28.50	D015665	1.50	0.163	0.163
			28.50	30.00	D015666	1.50	0.398	0.398
			30.00	31.50	D015667	1.50	0.438	0.438
			31.50	33.00	D015668	1.50	0.450	0.450
			33.00	34.50	D015669	1.50	0.206	0.206
			34.50	36.00	D015670	1.50	0.223	0.223
			36.00	37.50	D015671	1.50	0.083	0.083
			37.50	39.00	D015673	1.50	0.090	0.090
			39.00	40.50	D015674	1.50	0.068	0.068
			40.50	42.00	D015675	1.50	0.066	0.066
			42.00	43.50	D015676	1.50	0.746	0.746
			43.50	45.00	D015677	1.50	1.240	1.240
			45.00	46.50	D015678	1.50	1.375	1.375
			46.50	48.00	D015679	1.50	1.475	1.475
			48.00	49.50	D015681	1.50	0.138	0.138
			49.50	51.00	D015683	1.50	0.629	0.629
			51.00	52.50	D015684	1.50	0.496	0.496
			52.50	54.00	D015685	1.50	0.848	0.848
			54.00	55.50	D015686	1.50	3.150	3.150

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				55.50	57.00	D015687	1.50	0.164		0.164
				57.00	58.70	D015688	1.70	0.178		0.178
				58.70	60.00	D015689	1.30	0.126		0.126
				60.00	61.50	D015690	1.50	0.097		0.097
				61.50	63.00	D015691	1.50	0.010		0.010
				63.00	64.50	D015693	1.50	0.005		0.005
				64.50	66.00	D015694	1.50	<0.005		0.001
				66.00	67.50	D015695	1.50	0.006		0.006
				67.50	69.00	D015696	1.50	0.628		0.628
				69.00	70.50	D015697	1.50	0.894		0.894
				70.50	72.00	D015698	1.50	0.103		0.103
				72.00	73.50	D015699	1.50	0.163		0.163
				73.50	75.00	D015700	1.50	0.103		0.103
				75.00	76.50	D015701	1.50	0.093		0.093
				76.50	78.00	D015703	1.50	0.724		0.724
				78.00	79.50	D015704	1.50	0.468		0.468
				79.50	81.00	D015705	1.50	0.017		0.017
				81.00	82.50	D015706	1.50	0.014		0.014
				82.50	84.00	D015707	1.50	<0.005		0.001
				84.00	85.50	D015708	1.50	0.044		0.044
				85.50	87.00	D015709	1.50	0.206		0.206
				87.00	88.50	D015710	1.50	0.009		0.009
				88.50	90.00	D015711	1.50	0.020		0.020
				90.00	91.50	D015713	1.50	<0.005		0.001
				91.50	93.00	D015714	1.50	0.005		0.005
				93.00	94.50	D015715	1.50	0.019		0.019
				94.50	96.00	D015716	1.50	0.045		0.045
				96.00	97.50	D015717	1.50	0.091		0.091
				97.50	99.00	D015718	1.50	0.010		0.010
				99.00	100.50	D015719	1.50	0.029		0.029
100.43	100.63	CIS		100.50	102.00	D015721	1.50	0.028		0.028
		<b>Cisaillement 35°</b>		102.00	103.50	D015723	1.50	0.012		0.012
		Cisaillement d'intensité moyenne.		103.50	105.00	D015724	1.50	0.009		0.009
		La syénite est chloritisée et carbonatisée.								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
117.00	325.08	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique rougeâtre, violacée par endroits, parfois grisâtre, gris foncé, massive et assez homogène. Les porphyres de feldspaths se présentent surtout hypi à idiomorphes, zonés parfois. Ils présentent la forme de lattes, et parfois hexagonale (syénite à pruneaux). La syénite est hématisée et souvent carbonatisée. Plusieurs fractures occupées par des veinules de carbonates-albite, disposées entre 30°-80°ac et variant de 1-5mm en épaisseur. Présence de quelques veinules de quartz-carbonates-chlorite, ne dépassant 2cm en épaisseur.	105.00	106.50	D015725	1.50	0.005		0.005
			106.50	108.00	D015726	1.50	0.107		0.107
			108.00	109.50	D015727	1.50	0.165		0.165
			109.50	111.00	D015728	1.50	0.013		0.013
			111.00	112.50	D015729	1.50	0.126		0.126
			112.50	114.00	D015730	1.50	0.074		0.074
			114.00	115.50	D015731	1.50	0.101		0.101
			115.50	117.00	D015733	1.50	0.231		0.231
			117.00	118.50	D015734	1.50	0.089		0.089
			118.50	120.00	D015735	1.50	<0.005		0.001
			120.00	121.50	D015736	1.50	0.036		0.036
			121.50	123.00	D015737	1.50	0.024		0.024
			123.00	124.50	D015738	1.50	0.035		0.035
			124.50	126.00	D015739	1.50	0.010		0.010
			126.00	127.50	D015740	1.50	<0.005		0.001
			127.50	129.00	D015741	1.50	0.067		0.067
			129.00	130.50	D015743	1.50	0.125		0.125
129.10	129.70	CIS <b>Cisaillement 30°</b> Cisaillement d'intensité faible à moyenne. Présence de veinules de quartz-chlorite selon la déformation. La syénite est carbonatisée et chloritisée.	130.50	132.00	D015744	1.50	0.022		0.022
			132.00	133.50	D015745	1.50	0.124		0.124
			133.50	135.00	D015746	1.50	0.147		0.147
			135.00	136.50	D015747	1.50	0.216		0.216
			136.50	138.00	D015748	1.50	0.343		0.343
			138.00	139.50	D015749	1.50	0.071		0.071
			139.50	141.00	D015750	1.50	0.007		0.007
			141.00	142.50	D015751	1.50	0.107		0.107
			142.50	144.00	D015753	1.50	0.051		0.051
			144.00	145.50	D015754	1.50	0.005		0.005
			145.50	147.00	D015755	1.50	0.130		0.130
			147.00	148.50	D015756	1.50	<0.005		0.001
			148.50	150.00	D015757	1.50	<0.005		0.001
			150.00	151.50	D015758	1.50	0.007		0.007
			151.50	153.00	D015759	1.50	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			153.00	154.50	D015761	1.50		0.105
			154.50	156.00	D015763	1.50		0.086
			156.00	157.50	D015764	1.50		0.165
			157.50	159.00	D015765	1.50		<0.005
			159.00	160.50	D015766	1.50		0.225
			160.50	162.00	D015767	1.50		0.499
			162.00	163.50	D015768	1.50		0.153
			163.50	165.00	D015769	1.50		0.342
			165.00	166.50	D015770	1.50		0.123
			166.50	168.00	D015771	1.50		0.202
			168.00	169.50	D015773	1.50		0.043
			169.50	171.00	D015774	1.50		0.011
			171.00	172.50	D015775	1.50		0.014
			172.50	174.00	D015776	1.50		0.012
			174.00	175.50	D015777	1.50		<0.005
			175.50	177.00	D015778	1.50		0.076
			177.00	178.50	D015779	1.50		0.043
			178.50	180.00	D015780	1.50		0.035
			180.00	181.50	D015781	1.50		0.013
			181.50	183.00	D015783	1.50		0.014
			183.00	184.50	D015784	1.50		0.005
			184.50	186.00	D015785	1.50		0.133
			186.00	187.50	D015786	1.50		0.373
186.12	186.25	CIS	187.50	189.00	D015787	1.50		0.027
		<b>Cisaillement 45°</b>	189.00	190.50	D015788	1.50		0.011
		Cisaillement moyen, ayant une épaisseur d'environ 7cm.	190.50	192.00	D015789	1.50		0.021
		Pyrite (tr-1%) finemnt disséminée.	192.00	193.50	D015790	1.50		<0.005
		Présence de veinules de quartz-carbonates-chlorite.	193.50	195.00	D015791	1.50		<0.005
			195.00	196.50	D015793	1.50		0.005
			196.50	198.00	D015794	1.50		0.006
			198.00	199.50	D015795	1.50		0.147
			199.50	201.00	D015796	1.50		0.056
			201.00	202.50	D015797	1.50		<0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	202.50	204.00	D015798	1.50	0.014		0.014
	204.00	205.50	D015799	1.50	0.017		0.017
	205.50	207.00	D015800	1.50	0.008		0.008
	207.00	208.50	D015801	1.50	<0.005		0.001
	208.50	210.00	D015803	1.50	<0.005		0.001
	210.00	211.50	D015804	1.50	<0.005		0.001
	211.50	213.00	D015805	1.50	0.408		0.408
	213.00	214.50	D015806	1.50	0.317		0.317
	214.50	216.00	D015807	1.50	0.172		0.172
	216.00	217.50	D015808	1.50	0.289		0.289
	217.50	219.00	D015809	1.50	0.112		0.112
	219.00	220.50	D015810	1.50	0.028		0.028
	220.50	222.00	D015811	1.50	0.043		0.043
	222.00	223.50	D015813	1.50	<0.005		0.001
	223.50	225.00	D015814	1.50	<0.005		0.001
	225.00	226.50	D015815	1.50	0.005		0.005
	226.50	228.00	D015816	1.50	0.011		0.011
	228.00	229.50	D015817	1.50	0.008		0.008
	229.50	231.00	D015818	1.50	<0.005		0.001
	231.00	232.50	D015819	1.50	0.041		0.041
	232.50	234.00	D015820	1.50	0.005		0.005
	234.00	235.50	D015821	1.50	0.021		0.021
	235.50	237.00	D015823	1.50	0.022		0.022
	237.00	238.50	D015824	1.50	0.034		0.034
	238.50	240.00	D015825	1.50	0.005		0.005
	240.00	241.50	D015826	1.50	0.005		0.005
	241.50	243.00	D015827	1.50	<0.005		0.001
	243.00	244.50	D015828	1.50	<0.005		0.001
	244.50	246.00	D015829	1.50	<0.005		0.001
	246.00	247.50	D015830	1.50	0.157		0.157
	247.50	249.00	D015831	1.50	0.132		0.132
	249.00	250.50	D015833	1.50	0.315		0.315
	250.50	252.00	D015834	1.50	0.229		0.229

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			252.00	253.50	D015835	1.50	0.676		0.676
			253.50	255.00	D015836	1.50	0.041		0.041
			255.00	256.50	D015837	1.50	0.329		0.329
			256.50	258.00	D015838	1.50	0.077		0.077
			258.00	259.50	D015839	1.50	<0.005		0.001
			259.50	261.00	D015841	1.50	0.187		0.187
			261.00	262.50	D015843	1.50	0.005		0.005
			262.50	264.00	D015844	1.50	0.014		0.014
			264.00	265.50	D015845	1.50	0.055		0.055
			265.50	267.00	D015846	1.50	0.118		0.118
266.80	267.21	FAI	267.00	268.50	D015847	1.50	0.645	0.645	
		<b>Faille 25°</b>	268.50	270.00	D015848	1.50	0.219	0.219	
		Faille disposée entre 0°-20°ac.							
		Nous observons des fragments de syénite dans une matrice de chlorite.							
		Les épontes sont bréchifiées.							
269.55	270.12	CIS	270.00	271.50	D015849	1.50	0.025	0.025	
		<b>Cisaillement 20°</b>	271.50	273.00	D015850	1.50	0.064	0.064	
		Nous observons des cisaillements et injectés parfois de veinules de quartz-carbonates et chlorite.	273.00	274.50	D015851	1.50	<0.005	0.001	
		Ils ne dépassent 5cm en épaisseur.	274.50	276.00	D015853	1.50	<0.005	0.001	
		Les épontes sont parfois bréchifiées, fracturées dont le sinterstices sont occupées par de la chlorite et/ou tourmaline.	276.00	277.50	D015854	1.50	<0.005	0.001	
		Le système veiné est parfois minéralisé par un métal fin, argentifère (?), grisâtre.	277.50	279.00	D015855	1.50	<0.005	0.001	
		Pyrite (1-2%) très finement disséminée.	279.00	280.50	D015856	1.50	<0.005	0.001	
			280.50	282.00	D015857	1.50	<0.005	0.001	
			282.00	283.50	D015858	1.50	<0.005	0.001	
			283.50	285.00	D015859	1.50	<0.005	0.001	
			285.00	286.50	D015860	1.50	0.014	0.014	
			286.50	288.00	D015861	1.50	0.007	0.007	
			288.00	289.50	D015863	1.50	<0.005	0.001	
			289.50	291.00	D015864	1.50	<0.005	0.001	
			291.00	292.50	D015865	1.50	<0.005	0.001	
			292.50	294.00	D015866	1.50	<0.005	0.001	
			294.00	295.50	D015867	1.50	0.006	0.006	
			295.50	297.00	D015868	1.50	0.011	0.011	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
325.08	331.80	SY; POR <b>Syénite 30°; Porphyrique</b> Dyke de syénite porphyrique, à lattes, beige surtout et rosée ou ocre par endroits. Elle se compose de porphyres de feldspaths surtout idiomorphes et présentant la forme de lattes. La quantité est d'environ 15% et peuvent atteindre jusqu'à 0.5x3cm en dimensions. Certains sont altérés, zonés. Leur teinte est blanc, grisâtre et verdâtre. Nous observons plusieurs porphyres de feldspaths de faibles dimensions. La matrice est aphanitique. Ce dyke est fracturé par endroits et bréchique par endroits. Minéralisation de pyrite (1-2%) dans les fractures. Nous observons des veines de quartz-carbonates, stériles en sulfures et disposées entre 55°-75°ac. Présence d'un autre système de quartz, gris foncé, disposé entre 25°-35°ac et ne dépassant 2cm en épaisseur. Ces systèmes représentent environ 5% du volume de la carotte.	297.00	298.50	D015869	1.50	0.536		0.536
			298.50	300.00	D015870	1.50	0.006		0.006
			300.00	301.50	D015871	1.50	<0.005		0.001
			301.50	303.00	D015873	1.50	<0.005		0.001
			303.00	304.50	D015874	1.50	<0.005		0.001
			304.50	306.00	D015875	1.50	<0.005		0.001
			306.00	307.50	D015876	1.50	<0.005		0.001
			307.50	309.00	D015877	1.50	<0.005		0.001
			309.00	310.50	D015878	1.50	<0.005		0.001
			310.50	312.00	D015879	1.50	<0.005		0.001
			312.00	313.50	D015881	1.50	<0.005		0.001
			313.50	315.00	D015883	1.50	<0.005		0.001
			315.00	316.50	D015884	1.50	0.009		0.009
			316.50	318.00	D015885	1.50	0.080		0.080
			318.00	319.50	D015886	1.50	0.047		0.047
			319.50	321.00	D015887	1.50	<0.005		0.001
			321.00	322.50	D015888	1.50	0.016		0.016
			322.50	324.00	D015889	1.50	0.005		0.005
			324.00	325.08	D015890	1.08	0.064		0.064
			325.08	326.00	D015891	0.92	0.830		0.830
326.00	327.00	D015893	1.00	0.913		0.913			
327.00	328.50	D015894	1.50	0.264		0.264			
328.50	329.60	D015895	1.10	1.685		1.685			
329.60	330.70	D015896	1.10	1.065		1.065			
330.70	331.80	D015897	1.10	0.643		0.643			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
331.80	411.00	SY; POR	331.80	333.00	D015898	1.20	0.106		0.106
		<b>Syénite 55*; Porphyrique</b>	333.00	334.50	D015899	1.50	<0.005		0.001
		Syénite porphyrique altérée, rosâtre surtout, ocre et grisâtre par endroits.	334.50	336.00	D015900	1.50	<0.005		0.001
		Sa composition est assez homogène.	336.00	337.50	D015901	1.50	<0.005		0.001
		Elle est hématisée, dure.	337.50	339.00	D015903	1.50	<0.005		0.001
		La quantité de porphyre esrt variable.	339.00	340.50	D015904	1.50	<0.005		0.001
		Nous observons plusieurs fractures occupées par des veinules de carbonates-quartz.	340.50	342.00	D015905	1.50	<0.005		0.001
			342.00	343.50	D015906	1.50	<0.005		0.001
			343.50	345.00	D015907	1.50	<0.005		0.001
			345.00	346.50	D015908	1.50	0.007		0.007
			346.50	348.00	D015909	1.50	<0.005		0.001
			348.00	349.50	D015910	1.50	<0.005		0.001
			349.50	351.00	D015911	1.50	0.010		0.010
			351.00	352.50	D015913	1.50	<0.005		0.001
			352.50	354.00	D015914	1.50	0.138		0.138
			354.00	355.50	D015915	1.50	0.262		0.262
			355.50	357.00	D015916	1.50	0.212		0.212
			357.00	358.50	D015917	1.50	0.008		0.008
			358.50	360.00	D015918	1.50	<0.005		0.001
			360.00	361.50	D015919	1.50	<0.005		0.001
			361.50	363.00	D015921	1.50	<0.005		0.001
			363.00	364.50	D015922	1.50	<0.005		0.001
			364.50	366.00	D015923	1.50	<0.005		0.001
			366.00	367.50	D015924	1.50	<0.005		0.001
			367.50	369.00	D015925	1.50	<0.005		0.001
			369.00	370.50	D015926	1.50	0.036		0.036
			370.50	372.00	D015927	1.50	0.043		0.043
			372.00	373.50	D015928	1.50	<0.005		0.001
			373.50	375.00	D015929	1.50	<0.005		0.001
			375.00	376.50	D015930	1.50	<0.005		0.001
			376.50	378.00	D015931	1.50	0.016		0.016
			378.00	379.50	D015933	1.50	<0.005		0.001
			379.50	381.00	D015934	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	381.00	382.50	D015935	1.50	<0.005		0.001
	382.50	384.00	D015936	1.50	0.006		0.006
	384.00	385.50	D015937	1.50	<0.005		0.001
	385.50	387.00	D015938	1.50	<0.005		0.001
	387.00	388.50	D015939	1.50	<0.005		0.001
	388.50	390.00	D015940	1.50	<0.005		0.001
	390.00	391.50	D015941	1.50	<0.005		0.001
	391.50	393.00	D015943	1.50	<0.005		0.001
	393.00	394.50	D015944	1.50	<0.005		0.001
	394.50	396.00	D015945	1.50	<0.005		0.001
	396.00	397.50	D015946	1.50	<0.005		0.001
	397.50	399.00	D015947	1.50	<0.005		0.001
	399.00	400.50	D015948	1.50	<0.005		0.001
	400.50	402.00	D015949	1.50	<0.005		0.001
	402.00	403.50	D015950	1.50	<0.005		0.001
	403.50	405.00	D015951	1.50	0.091		0.091
	405.00	406.50	D015953	1.50	0.089		0.089
	406.50	408.00	D015954	1.50	0.012		0.012
	408.00	409.50	D015955	1.50	0.157		0.157
	409.50	411.00	D015956	1.50	0.033		0.033
411.00	Fin du sondage Nombre d'échantillons : 271 Nombre d'échantillons QAQC : 36 Longueur totale échantillonnée : 403.60						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.00	10.50	D015652	D015651	1.50	0.006	0.006
22.50	24.00	D015662	K	1.50	0.987	0.987
36.00	37.50	D015672	D015671	1.50	0.052	0.052
46.50	48.00	D015680	M1	1.50	0.005	0.005
48.00	49.50	D015682	L	1.50	2.470	2.470
61.50	63.00	D015692	D015691	1.50	0.010	0.010
75.00	76.50	D015702	M	1.50	3.010	3.010
88.50	90.00	D015712	D015711	1.50	0.021	0.021
99.00	100.50	D015720	M1	1.50	<0.005	0.001
100.50	102.00	D015722	J	1.50	0.760	0.760
114.00	115.50	D015732	D015731	1.50	0.087	0.087
127.50	129.00	D015742	K	1.50	0.966	0.966
141.00	142.50	D015752	D015751	1.50	0.118	0.118
151.50	153.00	D015760	M1	1.50	<0.005	0.001
153.00	154.50	D015762	L	1.50	2.200	2.200
166.50	168.00	D015772	D015771	1.50	0.194	0.194
180.00	181.50	D015782	M	1.50	2.660	2.660
193.50	195.00	D015792	D015791	1.50	<0.005	0.001
207.00	208.50	D015802	J	1.50	0.776	0.776
220.50	222.00	D015812	D015811	1.50	0.044	0.044
234.00	235.50	D015822	K	1.50	1.080	1.080
247.50	249.00	D015832	D015831	1.50	0.156	0.156
258.00	259.50	D015840	M1	1.50	<0.005	0.001
259.50	261.00	D015842	L	1.50	2.190	2.190
273.00	274.50	D015852	D015851	1.50	<0.005	0.001
286.50	288.00	D015862	M	1.50	3.220	3.220
300.00	301.50	D015872	D015871	1.50	<0.005	0.001
310.50	312.00	D015880	M1	1.50	<0.005	0.001
312.00	313.50	D015882	J	1.50	0.815	0.815
325.08	326.00	D015892	D015891	0.92	0.798	0.798
336.00	337.50	D015902	K	1.50	1.060	1.060
349.50	351.00	D015912	D015911	1.50	0.008	0.008
360.00	361.50	D015920	M1	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
376.50	378.00	D015932	D015931	1.50	0.014	0.014
390.00	391.50	D015942	M	1.50	3.320	3.320
403.50	405.00	D015952	D015951	1.50	0.070	0.070

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-184</b>	Titre minier :	Section :	630500
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-06-07	Date de description :	2010-06-18
	Au : 2010-06-10		

Collet

Azimut : 180.00°  
 Plongée : -45.00°  
 Longueur : 225.00 m

UTM

Est	630 499.7
Nord	5 374 198.5
Élévation	307.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	0.00°	0.00°	Oui
Reflex	3.00	218.30°	-45.90°	Oui
Reflex	6.00	350.60°	-46.00°	Oui
Reflex	9.00	302.00°	-46.00°	Oui
Reflex	12.00	338.70°	-46.00°	Oui
Reflex	15.00	324.90°	-45.90°	Oui
Reflex	18.00	336.00°	-45.80°	Oui
Reflex	21.00	70.70°	-45.40°	Oui
Reflex	24.00	179.90°	-45.20°	Non
Reflex	27.00	179.50°	-45.50°	Non
Reflex	30.00	180.40°	-45.10°	Non
Reflex	33.00	179.20°	-45.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	180.60°	-45.10°	Non
Reflex	39.00	180.10°	-45.10°	Non
Reflex	42.00	179.50°	-45.10°	Non
Reflex	45.00	180.30°	-45.00°	Non
Reflex	48.00	181.50°	-44.90°	Oui
Reflex	51.00	180.50°	-45.00°	Non
Reflex	54.00	180.40°	-45.00°	Non
Reflex	57.00	180.00°	-45.10°	Non
Reflex	60.00	181.30°	-44.80°	Non
Reflex	63.00	179.70°	-45.00°	Oui
Reflex	66.00	180.30°	-44.80°	Non
Reflex	69.00	180.10°	-44.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	72.00	180.60°	-44.60°	Non	Reflex	171.00	180.40°	-42.60°	Non
Reflex	75.00	179.50°	-45.00°	Oui	Reflex	174.00	180.70°	-42.50°	Non
Reflex	78.00	180.20°	-44.70°	Non	Reflex	177.00	180.10°	-42.50°	Non
Reflex	81.00	180.20°	-44.60°	Non	Reflex	180.00	180.90°	-42.40°	Non
Reflex	84.00	179.90°	-44.70°	Oui	Reflex	183.00	180.40°	-42.40°	Non
Reflex	87.00	180.40°	-44.60°	Non	Reflex	186.00	180.40°	-42.20°	Non
Reflex	90.00	180.20°	-44.60°	Non	Reflex	189.00	180.80°	-42.00°	Non
Reflex	93.00	180.60°	-44.70°	Non	Reflex	192.00	180.20°	-41.90°	Non
Reflex	96.00	180.50°	-44.50°	Non	Reflex	195.00	180.00°	-41.70°	Non
Reflex	99.00	180.00°	-44.50°	Non	Reflex	198.00	180.20°	-41.40°	Non
Reflex	102.00	179.50°	-44.60°	Oui	Reflex	201.00	180.30°	-41.40°	Non
Reflex	105.00	180.10°	-44.60°	Non	Reflex	204.00	180.10°	-41.30°	Non
Reflex	108.00	180.90°	-44.50°	Non	Reflex	207.00	180.40°	-41.30°	Non
Reflex	111.00	179.80°	-44.40°	Non	Reflex	210.00	180.10°	-41.30°	Non
Reflex	114.00	180.10°	-44.40°	Non	Reflex	213.00	180.60°	-41.20°	Non
Reflex	117.00	177.20°	-44.30°	Oui	Reflex	216.00	180.50°	-41.20°	Non
Reflex	120.00	180.10°	-44.20°	Non	Reflex	219.00	180.80°	-41.10°	Non
Reflex	123.00	179.70°	-44.20°	Non	Reflex	222.00	180.60°	-41.00°	Non
Reflex	126.00	180.80°	-44.00°	Non	Reflex	225.00	180.80°	-41.00°	Non
Reflex	129.00	179.90°	-44.00°	Non					
Reflex	132.00	179.80°	-43.90°	Non					
Reflex	135.00	180.00°	-43.70°	Non					
Reflex	138.00	180.20°	-43.50°	Non					
Reflex	141.00	180.30°	-43.40°	Non					
Reflex	144.00	180.40°	-43.40°	Non					
Reflex	147.00	179.70°	-43.30°	Non					
Reflex	150.00	180.20°	-43.20°	Non					
Reflex	153.00	180.10°	-43.20°	Non					
Reflex	156.00	180.80°	-43.20°	Non					
Reflex	159.00	180.40°	-43.10°	Non					
Reflex	162.00	180.50°	-42.90°	Non					
Reflex	165.00	180.10°	-42.80°	Non					
Reflex	168.00	180.50°	-42.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	17.00	MT							
		<b>Mort-terrain</b>							
17.00	29.40	SY; MAS	17.00	18.50	D027560	1.50	0.018		0.018
		<b>Syénite; Roche massive</b>	18.50	20.00	D027561	1.50	0.117		0.117
		massive grenue, localement bréchifié, hématisation, oxydes de carbonâtes, séricite, chlorite PY fine diss	20.00	21.50	D027562	1.50	0.530		0.530
			21.50	23.00	D027563	1.50	0.241		0.241
			23.00	24.50	D027564	1.50	0.506		0.506
			24.50	26.00	D027565	1.50	1.700		1.700
			26.00	27.40	D027566	1.40	0.666		0.666
			27.40	28.40	D027567	1.00	0.020		0.020
			28.40	29.40	D027568	1.00	0.013		0.013
29.40	30.00	NR							
		<b>Carotte perdue</b>							
30.00	32.50	SY; MAS; FIN	30.00	31.50	D027570	1.50	0.072		0.072
		<b>Syénite; Roche massive; Grains fins</b>	31.50	32.50	D027571	1.00	0.018		0.018
		massive grenue, localement bréchifié, hématisation, oxydes de carbonâtes, séricite, chlorite PY fine diss							
32.50	33.00	NR							
		<b>Carotte perdue</b>							
33.00	34.40	SY; MAS; FIN	33.00	34.40	D027572	1.40	0.044		0.044
		<b>Syénite; Roche massive; Grains fins</b>							
		massive grenue, localement bréchifié, hématisation, oxydes de carbonâtes, séricite, chlorite PY fine diss							
34.40	36.00	NR							
		<b>Carotte perdue</b>							
36.00	51.40	SY; MAS	36.00	37.50	D027573	1.50	0.138		0.138
		<b>Syénite; Roche massive</b>	37.50	39.00	D027574	1.50	0.453		0.453
		massive grenue, localement bréchifié, hématisation, oxydes de carbonâtes, séricite, chlorite PY fine diss	39.00	40.50	D027575	1.50	0.089		0.089
			40.50	42.00	D027576	1.50	0.134		0.134
			42.00	43.50	D027577	1.50	0.147		0.147
			43.50	45.00	D027578	1.50	0.782		0.782
			45.00	46.30	D027580	1.30	0.187		0.187
			46.30	47.30	D027581	1.00	0.049		0.049
			47.30	48.80	D027582	1.50	2.000		2.000
			48.80	50.30	D027583	1.50	2.580		2.580

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
51.40	54.30	TU; RUB; LAM <b>Tuf à cendre/lapillis 40°; Rubané; Laminations parallèles</b> litage, fines laminations, pseudo foliation, , carbonates, CL+++ , SR+++ , calcite	50.30	51.40	D027584	1.10	1.405		1.405
			51.40	52.80	D027585	1.40	0.220		0.220
52.60	52.63	FAI <b>Faille 40°</b> boue de faille verdâtre	52.80	54.30	D027586	1.50	0.092		0.092
54.30	55.00	NR <b>Carotte perdue</b>							
55.00	87.10	TU; LAM; RUB <b>Tuf à cendre/lapillis; Laminations parallèles; Rubané</b> litage, fines laminations, pseudo foliation, carbonates, CL+++ , SR+++ , calcite	55.00	56.50	D027587	1.50	0.020		0.020
			56.50	58.00	D027588	1.50	0.021		0.021
			58.00	59.50	D027590	1.50	0.024		0.024
55.00	55.20	FRC <b>Fracturé</b> fragment cm							
58.30	58.40	FAI <b>Faille 50°</b> faillé et grindé	59.50	61.00	D027591	1.50	0.190		0.190
61.00	61.20	FRC <b>Fracturé</b> fragments cm	61.00	62.50	D027592	1.50	0.009		0.009
			62.50	64.00	D027593	1.50	0.073		0.073
63.50	64.00	FRC <b>Fracturé</b>	64.00	65.50	D027594	1.50	0.008		0.008
			65.50	67.00	D027595	1.50	0.008		0.008
			67.00	68.50	D027597	1.50	0.008		0.008
			68.50	70.00	D027598	1.50	0.057		0.057
			70.00	71.50	D027600	1.50	0.030		0.030
			71.50	73.00	D027601	1.50	0.030		0.030
			73.00	74.50	D027602	1.50	0.027		0.027
			74.50	76.00	D027603	1.50	0.042		0.042
			76.00	77.50	D027604	1.50	0.014		0.014
			77.50	79.00	D027605	1.50	0.011		0.011
			79.00	80.50	D027606	1.50	0.005		0.005
			80.50	82.00	D027607	1.50	<0.005		0.001
			82.00	83.50	D027608	1.50	0.005		0.005
			83.50	85.00	D027610	1.50	0.020		0.020



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
87.10	99.20	UM; RUB <b>Ultramafite serpentinisée 40°; Rubané</b> localement massive, cisailé et localement sub bréchique, veinules et cheveux de carbonâtes, talc, CL++, localement magnétique	85.00	86.00	D027611	1.00	0.024		0.024
			86.00	87.10	D027612	1.10	0.059		0.059
			87.10	88.50	D027613	1.40	0.074		0.074
			88.50	90.00	D027614	1.50	0.016		0.016
89.80	90.00	FRC <b>Fracturé</b> fragments cm	90.00	91.50	D027615	1.50	<0.005		0.001
90.20	91.90	FAI <b>Faille 30°</b> zone de faille avec boue verdâtre, fragments cm	91.50	93.00	D027616	1.50	<0.005		0.001
			93.00	94.50	D027617	1.50	<0.005		0.001
			94.50	96.00	D027618	1.50	<0.005		0.001
			96.00	97.50	D027620	1.50	<0.005		0.001
			97.50	99.20	D027621	1.70	<0.005		0.001
99.20	102.00	GR <b>Grès 50°</b> grès à grains fin, lité, à laminations de séricite et chlorite, altération en séricite et chlorite	99.20	100.50	D027622	1.30	0.007		0.007
			100.50	102.00	D027623	1.50	0.006		0.006
102.00	104.80	UM; RUB <b>Ultramafite serpentinisée 50°; Rubané</b> cisaillement, passablement bréchifié localement, passablement schisteuse, talc, CL++, localement spinifex	102.00	103.50	D027624	1.50	<0.005		0.001
			103.50	105.00	D027625	1.50	<0.005		0.001
104.80	225.00	GR; LAM <b>Grès 50°; Laminations parallèles</b> localement massif et cisailé, litage ( lits à QZ-FP et mudstone) passablement plissé, avec alternance de niveau séricité et chlorité, localement intercalations de galets et fragments ou bloc sub automorphe, veines de QZ et carbonâtes	105.00	106.50	D027626	1.50	<0.005		0.001
			106.50	108.00	D027627	1.50	<0.005		0.001
107.10	107.15	FAI <b>Faille 60°</b> boue verdâtre	108.00	109.50	D027628	1.50	<0.005		0.001
			109.50	111.00	D027630	1.50	<0.005		0.001
			111.00	112.00	D027631	1.00	<0.005		0.001
			112.00	113.50	D027632	1.50	0.020		0.020
			113.50	115.00	D027633	1.50	0.021		0.021
			115.00	116.50	D027634	1.50	0.040		0.040
			116.50	118.00	D027635	1.50	0.030		0.030
			118.00	119.50	D027637	1.50	0.014		0.014
			119.50	121.00	D027638	1.50	0.043		0.043

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	121.00	122.50	D027640	1.50	0.005		0.005
	122.50	124.00	D027641	1.50	<0.005		0.001
	124.00	125.50	D027642	1.50	0.007		0.007
	125.50	127.00	D027643	1.50	0.008		0.008
	127.00	128.60	D027644	1.60	0.008		0.008
	128.60	130.00	D027645	1.40	0.015		0.015
	130.00	131.50	D027646	1.50	0.016		0.016
	131.50	132.90	D027647	1.40	0.076		0.076
	132.90	134.50	D027648	1.60	0.007		0.007
	134.50	136.00	D027650	1.50	0.005		0.005
	136.00	137.50	D027651	1.50	0.028		0.028
	137.50	139.00	D027652	1.50	0.009		0.009
	139.00	140.50	D027653	1.50	0.021		0.021
	140.50	142.00	D027654	1.50	0.030		0.030
	142.00	143.50	D027655	1.50	0.101		0.101
	143.50	145.00	D027656	1.50	0.112		0.112
	145.00	146.50	D027657	1.50	0.006		0.006
	146.50	148.00	D027658	1.50	<0.005		0.001
	148.00	149.50	D027660	1.50	0.006		0.006
	149.50	151.00	D027661	1.50	0.007		0.007
	151.00	152.50	D027662	1.50	0.021		0.021
	152.50	154.00	D027663	1.50	<0.005		0.001
	154.00	155.50	D027664	1.50	0.006		0.006
	155.50	157.00	D027665	1.50	0.009		0.009
	157.00	158.50	D027666	1.50	0.127		0.127
	158.50	160.00	D027667	1.50	0.111		0.111
	160.00	161.50	D027668	1.50	0.092		0.092
	161.50	163.00	D027670	1.50	0.162		0.162
	163.00	164.50	D027671	1.50	0.017		0.017
	164.50	166.00	D027672	1.50	0.012		0.012
	166.00	167.50	D027673	1.50	0.074		0.074
	167.50	169.00	D027674	1.50	0.014		0.014
	169.00	170.50	D027675	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	170.50	172.00	D027677	1.50	<0.005		0.001
	172.00	173.50	D027678	1.50	0.006		0.006
	173.50	175.00	D027680	1.50	<0.005		0.001
	175.00	176.50	D027681	1.50	0.005		0.005
	176.50	178.00	D027682	1.50	0.006		0.006
	178.00	179.50	D027683	1.50	0.005		0.005
	179.50	181.00	D027684	1.50	0.006		0.006
	181.00	182.50	D027685	1.50	0.007		0.007
	182.50	184.00	D027686	1.50	<0.005		0.001
	184.00	185.50	D027687	1.50	0.008		0.008
	185.50	187.00	D027688	1.50	0.049		0.049
	187.00	188.50	D027690	1.50	0.014		0.014
	188.50	190.00	D027691	1.50	0.068		0.068
	190.00	191.50	D027692	1.50	0.025		0.025
	191.50	193.00	D027693	1.50	0.039		0.039
	193.00	194.50	D027694	1.50	0.238		0.238
	194.50	196.00	D027695	1.50	0.011		0.011
	196.00	197.50	D027696	1.50	0.008		0.008
	197.50	199.00	D027697	1.50	0.006		0.006
	199.00	200.50	D027698	1.50	0.005		0.005
	200.50	202.00	D027700	1.50	0.006		0.006
	202.00	203.50	D027701	1.50	0.007		0.007
	203.50	205.00	D027702	1.50	0.007		0.007
	205.00	206.50	D027703	1.50	<0.005		0.001
	206.50	208.00	D027704	1.50	0.019		0.019
	208.00	209.50	D027705	1.50	0.006		0.006
	209.50	211.00	D027706	1.50	0.024		0.024
	211.00	212.50	D027707	1.50	0.017		0.017
	212.50	214.00	D027708	1.50	0.038		0.038
	214.00	215.50	D027710	1.50	0.014		0.014
	215.50	217.00	D027711	1.50	<0.005		0.001
	217.00	218.50	D027712	1.50	0.007		0.007
	218.50	220.00	D027713	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	220.00	221.50	D027714	1.50	0.011		0.011
	221.50	223.00	D027715	1.50	0.008		0.008
	223.00	224.00	D027717	1.00	0.010		0.010
	224.00	225.00	D027718	1.00	0.009		0.009
225.00      Fin du sondage Nombre d'échantillons : 140 Nombre d'échantillons QAQC : 20 Longueur totale échantillonnée : 204.60							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
28.40	29.40	D027569	D027568	1.00	0.012	0.012
43.50	43.50	D027579	J	0.00	0.785	0.785
56.50	58.00	D027589	D027588	1.50	0.024	0.024
65.50	65.50	D027596	M1	0.00	<0.005	0.001
68.50	68.50	D027599	K	0.00	1.120	1.120
82.00	83.50	D027609	D027608	1.50	<0.005	0.001
94.50	94.50	D027619	L	0.00	2.390	2.390
108.00	109.50	D027629	D027628	1.50	<0.005	0.001
116.50	116.50	D027636	M1	0.00	<0.005	0.001
119.50	119.50	D027639	M	0.00	3.010	3.010
132.90	134.50	D027649	D027648	1.60	0.008	0.008
146.50	146.50	D027659	J	0.00	0.738	0.738
160.00	161.50	D027669	D027668	1.50	0.069	0.069
169.00	169.00	D027676	M1	0.00	<0.005	0.001
172.00	172.00	D027679	K	0.00	0.673	0.673
185.50	187.00	D027689	D027688	1.50	0.033	0.033
199.00	199.00	D027699	L	0.00	2.010	2.010
212.50	214.00	D027709	D027708	1.50	0.094	0.094
221.50	221.50	D027716	M1	0.00	<0.005	0.001
224.00	224.00	D027719	M	0.00	3.060	3.060



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.80°	-59.60°	Non
Reflex	77.00	0.80°	-59.60°	Non
Reflex	80.00	1.50°	-59.60°	Non
Reflex	83.00	2.10°	-59.60°	Non
Reflex	86.00	1.40°	-59.50°	Non
Reflex	89.00	1.20°	-59.50°	Non
Reflex	92.00	1.10°	-59.50°	Non
Reflex	95.00	0.80°	-59.50°	Non
Reflex	98.00	0.90°	-59.50°	Non
Reflex	101.00	1.00°	-59.40°	Non
Reflex	104.00	1.20°	-59.40°	Non
Reflex	107.00	1.80°	-59.40°	Non
Reflex	110.00	1.60°	-59.40°	Non
Reflex	113.00	4.40°	-59.40°	Oui
Reflex	116.00	3.60°	-59.40°	Non
Reflex	119.00	4.00°	-59.40°	Non
Reflex	122.00	2.00°	-59.40°	Non
Reflex	125.00	2.40°	-59.30°	Non
Reflex	128.00	1.70°	-59.30°	Non
Reflex	131.00	2.00°	-59.30°	Non
Reflex	134.00	1.00°	-59.30°	Non
Reflex	137.00	2.40°	-59.20°	Non
Reflex	140.00	1.10°	-59.20°	Non
Reflex	143.00	3.40°	-59.20°	Non
Reflex	146.00	3.30°	-59.20°	Non
Reflex	149.00	3.40°	-59.20°	Non
Reflex	152.00	4.70°	-59.20°	Non
Reflex	155.00	5.10°	-59.20°	Non
Reflex	158.00	3.80°	-59.10°	Non
Reflex	161.00	1.60°	-59.10°	Oui
Reflex	164.00	3.50°	-59.10°	Non
Reflex	167.00	4.40°	-59.00°	Non
Reflex	170.00	5.10°	-59.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	1.80°	-59.00°	Non
Reflex	176.00	1.30°	-58.90°	Non
Reflex	179.00	2.80°	-58.90°	Non
Reflex	182.00	4.70°	-58.90°	Non
Reflex	185.00	2.70°	-58.90°	Non
Reflex	188.00	4.30°	-58.90°	Non
Reflex	191.00	4.60°	-58.90°	Non
Reflex	194.00	6.00°	-58.90°	Non
Reflex	197.00	4.70°	-58.80°	Non
Reflex	200.00	4.20°	-58.80°	Non
Reflex	203.00	5.00°	-58.80°	Non
Reflex	206.00	4.20°	-58.80°	Non
Reflex	209.00	4.20°	-58.70°	Non
Reflex	212.00	5.20°	-58.70°	Non
Reflex	215.00	3.90°	-58.70°	Non
Reflex	218.00	4.70°	-58.70°	Non
Reflex	221.00	4.00°	-58.60°	Non
Reflex	224.00	3.60°	-58.70°	Non
Reflex	227.00	4.90°	-58.60°	Non
Reflex	230.00	2.50°	-58.60°	Oui
Reflex	233.00	5.70°	-58.60°	Non
Reflex	236.00	6.30°	-58.60°	Non
Reflex	239.00	4.70°	-58.60°	Non
Reflex	242.00	5.50°	-58.60°	Non
Reflex	245.00	6.30°	-58.50°	Non
Reflex	248.00	4.60°	-58.50°	Non
Reflex	251.00	6.90°	-58.50°	Non
Reflex	254.00	4.60°	-58.50°	Non
Reflex	257.00	6.40°	-58.40°	Non
Reflex	260.00	7.10°	-58.40°	Non
Reflex	263.00	5.20°	-58.40°	Non
Reflex	266.00	6.00°	-58.30°	Non
Reflex	269.00	6.00°	-58.30°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	7.60°	-58.30°	Non	Reflex	371.00	7.60°	-57.90°	Non
Reflex	275.00	7.30°	-58.30°	Non	Reflex	374.00	8.50°	-57.90°	Non
Reflex	278.00	7.70°	-58.30°	Non	Reflex	377.00	8.10°	-57.90°	Non
Reflex	281.00	7.80°	-58.30°	Non	Reflex	380.00	8.30°	-57.90°	Non
Reflex	284.00	8.50°	-58.30°	Non	Reflex	383.00	6.80°	-57.90°	Non
Reflex	287.00	7.30°	-58.30°	Non	Reflex	386.00	9.50°	-57.80°	Non
Reflex	290.00	6.50°	-58.30°	Non	Reflex	389.00	10.60°	-57.80°	Non
Reflex	293.00	6.90°	-58.30°	Non	Reflex	392.00	9.30°	-57.80°	Non
Reflex	296.00	8.30°	-58.30°	Non	Reflex	395.00	9.30°	-57.80°	Non
Reflex	299.00	9.60°	-58.30°	Non	Reflex	398.00	10.00°	-57.80°	Non
Reflex	302.00	11.80°	-58.30°	Oui	Reflex	401.00	10.90°	-57.80°	Non
Reflex	305.00	9.00°	-58.30°	Non	Reflex	404.00	5.30°	-57.80°	Oui
Reflex	308.00	9.00°	-58.30°	Non	Reflex	407.00	9.30°	-57.70°	Non
Reflex	311.00	8.60°	-58.30°	Non	Reflex	410.00	7.10°	-57.70°	Non
Reflex	314.00	9.50°	-58.30°	Non	Reflex	413.00	7.70°	-57.70°	Non
Reflex	317.00	9.40°	-58.30°	Non	Reflex	416.00	7.10°	-57.60°	Non
Reflex	320.00	8.70°	-58.20°	Non	Reflex	419.00	7.70°	-57.60°	Non
Reflex	323.00	8.90°	-58.20°	Non	Reflex	422.00	7.90°	-57.50°	Non
Reflex	326.00	9.70°	-58.20°	Non	Reflex	425.00	8.20°	-57.50°	Non
Reflex	329.00	9.60°	-58.20°	Non	Reflex	428.00	8.40°	-57.50°	Non
Reflex	332.00	8.10°	-58.20°	Non	Reflex	431.00	8.30°	-57.40°	Non
Reflex	335.00	10.20°	-58.10°	Non	Reflex	434.00	8.50°	-57.40°	Non
Reflex	338.00	5.40°	-58.10°	Oui	Reflex	437.00	8.50°	-57.40°	Non
Reflex	341.00	9.10°	-58.10°	Non	Reflex	440.00	8.50°	-57.40°	Non
Reflex	344.00	6.00°	-58.10°	Non					
Reflex	347.00	6.20°	-58.10°	Non					
Reflex	350.00	6.60°	-58.00°	Non					
Reflex	353.00	10.30°	-58.00°	Non					
Reflex	356.00	9.40°	-58.00°	Non					
Reflex	359.00	9.10°	-58.00°	Non					
Reflex	362.00	8.80°	-57.90°	Non					
Reflex	365.00	8.50°	-57.90°	Non					
Reflex	368.00	7.80°	-57.90°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.40	MT						
		<b>Mort-terrain</b>						
1.40	414.80	SY; MAS; MTY; FIN	1.40	3.00	D004599	1.60	0.059	0.059
		<b>Syénite; Roche massive; Grains moyens; Grains fins</b>	3.00	4.50	D004600	1.50	0.017	0.017
		grenue à grains moyen à fin, localement altération en silice, localement magnétique, vacuoles, carbonâtes, HM++, SR+, CL+, oxyde de carbonâtes, calcite, PY fine irrég diss	4.50	6.00	D004601	1.50	0.151	0.151
			6.00	7.50	D004602	1.50	0.060	0.060
			7.50	9.00	D004603	1.50	0.005	0.005
			9.00	10.50	D004604	1.50	<0.005	0.001
			10.50	12.00	D004605	1.50	0.011	0.011
			12.00	13.50	D004606	1.50	0.013	0.013
			13.50	15.00	D004607	1.50	<0.005	0.001
			15.00	16.20	D004609	1.20	0.010	0.010
			16.20	17.20	D004610	1.00	0.006	0.006
			17.20	18.50	D004611	1.30	0.006	0.006
			18.50	20.00	D004612	1.50	0.108	0.108
			20.00	21.50	D004613	1.50	0.205	0.205
			21.50	23.00	D004614	1.50	1.625	1.625
			23.00	24.50	D004615	1.50	0.473	0.473
			24.50	26.00	D004616	1.50	0.333	0.333
			26.00	27.50	D004617	1.50	0.114	0.114
			27.50	29.00	D004619	1.50	0.127	0.127
			29.00	30.50	D004620	1.50	0.008	0.008
			30.50	32.00	D004621	1.50	0.045	0.045
			32.00	33.50	D004622	1.50	0.006	0.006
			33.50	35.00	D004623	1.50	5.400	5.400
			35.00	36.50	D004624	1.50	0.983	0.983
			36.50	38.00	D004625	1.50	0.070	0.070
			38.00	39.50	D004626	1.50	0.456	0.456
			39.50	41.00	D004627	1.50	<0.005	0.001
			41.00	42.50	D004629	1.50	0.027	0.027
			42.50	44.00	D004630	1.50	0.007	0.007
			44.00	45.50	D004631	1.50	0.057	0.057
			45.50	47.00	D004632	1.50	0.212	0.212
			47.00	48.50	D004633	1.50	0.013	0.013

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			48.50	50.00	D004634	1.50		0.015		0.015
			50.00	51.50	D004636	1.50		0.005		0.005
			51.50	53.00	D004637	1.50		0.019		0.019
			53.00	54.50	D004639	1.50		<0.005		0.001
			54.50	56.00	D004640	1.50		0.005		0.005
			56.00	57.50	D004641	1.50		1.190		1.190
			57.50	59.00	D004642	1.50		0.386		0.386
			59.00	60.50	D004643	1.50		0.015		0.015
			60.50	62.00	D004644	1.50		0.017		0.017
			62.00	63.50	D004645	1.50		0.014		0.014
			63.50	65.00	D004646	1.50		0.052		0.052
			65.00	66.50	D004647	1.50		<0.005		0.001
			66.50	68.00	D004649	1.50		<0.005		0.001
			68.00	69.50	D004650	1.50		0.008		0.008
			69.50	71.00	D004651	1.50		0.005		0.005
1.40	17.20	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP blanchâtre, grossier ± 0.3-3 cm sub automorphe à automorphe, zonés								
70.00	104.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe à sub automorphe, 0.2-0.5 cm	71.00	72.50	D004652	1.50		<0.005		0.001
			72.50	74.00	D004653	1.50		0.005		0.005
			74.00	75.50	D004654	1.50		<0.005		0.001
			75.50	77.00	D004655	1.50		<0.005		0.001
			77.00	78.50	D004656	1.50		<0.005		0.001
			78.50	80.00	D004657	1.50		<0.005		0.001
			80.00	81.50	D004659	1.50		<0.005		0.001
			81.50	83.00	D004660	1.50		<0.005		0.001
			83.00	84.50	D004661	1.50		0.005		0.005
			84.50	86.00	D004662	1.50		0.006		0.006
			86.00	87.50	D004663	1.50		0.005		0.005
			87.50	89.00	D004664	1.50		<0.005		0.001
			89.00	90.50	D004665	1.50		0.134		0.134
			90.50	92.00	D004666	1.50		<0.005		0.001
			92.00	93.50	D004667	1.50		0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	93.50	95.00	D004669	1.50	0.118		0.118
	95.00	96.50	D004670	1.50	<0.005		0.001
	96.50	97.50	D004671	1.00	<0.005		0.001
	97.50	98.70	D004672	1.20	0.024		0.024
	98.70	100.00	D004673	1.30	0.525		0.525
	100.00	101.50	D004674	1.50	0.038		0.038
	101.50	103.00	D004676	1.50	0.044		0.044
	103.00	104.50	D004677	1.50	0.395		0.395
	104.50	106.00	D004679	1.50	0.075		0.075
	106.00	107.50	D004680	1.50	1.765		1.765
	107.50	109.00	D004681	1.50	0.809		0.809
	109.00	110.50	D004682	1.50	2.630		2.630
	110.50	111.50	D004683	1.00	1.355		1.355
	111.50	113.00	D004684	1.50	0.008		0.008
	113.00	114.50	D004685	1.50	0.016		0.016
	114.50	116.00	D004686	1.50	0.009		0.009
	116.00	117.50	D004687	1.50	<0.005		0.001
	117.50	119.00	D004689	1.50	0.006		0.006
	119.00	120.50	D004690	1.50	0.078		0.078
	120.50	122.00	D004691	1.50	0.007		0.007
	122.00	123.50	D004692	1.50	0.056		0.056
	123.50	125.00	D004693	1.50	0.005		0.005
	125.00	126.50	D004694	1.50	<0.005		0.001
	126.50	128.00	D004695	1.50	0.005		0.005
	128.00	129.50	D004696	1.50	0.005		0.005
	129.50	131.00	D004697	1.50	0.119		0.119
	131.00	132.50	D004699	1.50	2.290		2.290
	132.50	134.00	D004700	1.50	0.085		0.085
	134.00	135.50	D004701	1.50	0.024		0.024
	135.50	137.00	D004702	1.50	0.008		0.008
	137.00	138.50	D004703	1.50	0.009		0.009
	138.50	140.00	D004704	1.50	0.033		0.033
	140.00	141.50	D004705	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
158.00	179.00	SY; POR <b>Syérite; Porphyrique</b> phénocristaux de Feldspaths blanchâtre ± 0.3-2 cm automorphe localement étiréen "lattes", HM++, SR++, oxydes de carbonâte	141.50	143.00	D004706	1.50	0.015		0.015
			143.00	144.50	D004707	1.50	0.005		0.005
			144.50	146.00	D004709	1.50	0.012		0.012
			146.00	147.50	D004710	1.50	0.109		0.109
			147.50	149.00	D004711	1.50	0.025		0.025
			149.00	150.50	D004712	1.50	0.005		0.005
			150.50	152.00	D004713	1.50	0.007		0.007
			152.00	153.50	D004714	1.50	0.107		0.107
			153.50	155.00	D004716	1.50	0.009		0.009
			155.00	156.50	D004717	1.50	0.061		0.061
			156.50	158.00	D004719	1.50	<0.005		0.001
			158.00	159.50	D004720	1.50	0.860		0.860
			159.50	161.00	D004721	1.50	1.400		1.400
			161.00	162.50	D004722	1.50	2.600		2.600
			162.50	164.00	D004723	1.50	0.024		0.024
			164.00	165.50	D004724	1.50	0.058		0.058
			165.50	167.00	D004725	1.50	1.445		1.445
			167.00	168.50	D004726	1.50	0.006		0.006
			168.50	170.00	D004727	1.50	0.006		0.006
			170.00	171.50	D004729	1.50	<0.005		0.001
			171.50	173.00	D004730	1.50	0.005		0.005
			173.00	174.50	D004731	1.50	0.021		0.021
			174.50	176.00	D004732	1.50	0.007		0.007
			176.00	177.50	D004733	1.50	0.033		0.033
			177.50	179.00	D004734	1.50	<0.005		0.001
			179.00	180.50	D004735	1.50	0.011		0.011
			180.50	182.00	D004736	1.50	0.009		0.009
			182.00	183.50	D004737	1.50	<0.005		0.001
			183.50	185.00	D004739	1.50	<0.005		0.001
			185.00	186.50	D004740	1.50	<0.005		0.001
186.50	188.00	D004741	1.50	<0.005		0.001			
188.00	189.50	D004742	1.50	0.006		0.006			
189.50	191.00	D004743	1.50	0.327		0.327			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	191.00	192.50	D004744	1.50	0.091		0.091
	192.50	194.00	D004745	1.50	0.057		0.057
	194.00	195.50	D004746	1.50	0.455		0.455
	195.50	197.00	D004747	1.50	0.025		0.025
	197.00	198.00	D004749	1.00	0.028		0.028
	198.00	199.00	D004750	1.00	0.006		0.006
	199.00	200.20	D004751	1.20	<0.005		0.001
	200.20	201.50	D004752	1.30	0.005		0.005
	201.50	203.00	D004753	1.50	0.042		0.042
	203.00	204.50	D004754	1.50	<0.005		0.001
	204.50	206.00	D004756	1.50	0.050		0.050
	206.00	207.50	D004757	1.50	0.062		0.062
	207.50	209.00	D004759	1.50	0.007		0.007
	209.00	210.50	D004760	1.50	0.022		0.022
	210.50	212.00	D004761	1.50	<0.005		0.001
	212.00	213.50	D004762	1.50	0.005		0.005
	213.50	215.00	D004763	1.50	0.044		0.044
	215.00	216.50	D004764	1.50	0.928		0.928
	216.50	218.00	D004765	1.50	0.229		0.229
	218.00	219.50	D004766	1.50	0.005		0.005
	219.50	221.00	D004767	1.50	0.006		0.006
	221.00	222.50	D004769	1.50	0.039		0.039
	222.50	224.00	D004770	1.50	0.009		0.009
	224.00	225.50	D004771	1.50	0.023		0.023
	225.50	227.00	D004772	1.50	0.137		0.137
	227.00	228.50	D004773	1.50	0.022		0.022
	228.50	230.00	D004774	1.50	1.055		1.055
	230.00	231.50	D004775	1.50	1.650		1.650
	231.50	233.00	D004776	1.50	0.344		0.344
	233.00	234.50	D004777	1.50	0.841		0.841
	234.50	236.00	D004779	1.50	0.277		0.277
	236.00	237.50	D004780	1.50	0.191		0.191
	237.50	239.00	D004781	1.50	0.154		0.154

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	239.00	240.50	D004782	1.50	0.010		0.010
	240.50	242.00	D004783	1.50	0.026		0.026
	242.00	243.50	D004784	1.50	0.051		0.051
	243.50	245.00	D004785	1.50	0.163		0.163
	245.00	246.50	D004786	1.50	0.279		0.279
	246.50	248.00	D004787	1.50	0.012		0.012
	248.00	249.50	D004789	1.50	0.020		0.020
	249.50	251.00	D004790	1.50	0.005		0.005
	251.00	252.50	D004791	1.50	0.007		0.007
	252.50	254.00	D004792	1.50	0.009		0.009
	254.00	255.50	D004793	1.50	0.050		0.050
	255.50	257.00	D004794	1.50	0.024		0.024
	257.00	258.50	D004796	1.50	0.055		0.055
	258.50	260.00	D004797	1.50	0.035		0.035
	260.00	261.50	D004799	1.50	0.888		0.888
	261.50	263.00	D004800	1.50	0.506		0.506
	263.00	264.50	D004801	1.50	0.069		0.069
	264.50	266.00	D004802	1.50	0.040		0.040
	266.00	267.50	D004803	1.50	0.025		0.025
	267.50	269.00	D004804	1.50	0.045		0.045
	269.00	270.50	D004805	1.50	0.103		0.103
	270.50	272.00	D004806	1.50	0.537		0.537
	272.00	273.50	D004807	1.50	0.038		0.038
	273.50	275.00	D004809	1.50	0.060		0.060
	275.00	276.50	D004810	1.50	0.006		0.006
	276.50	278.00	D004811	1.50	0.023		0.023
	278.00	279.50	D004812	1.50	0.029		0.029
	279.50	281.00	D004813	1.50	0.008		0.008
	281.00	282.50	D004814	1.50	0.049		0.049
	282.50	284.00	D004815	1.50	0.017		0.017
	284.00	285.50	D004816	1.50	0.245		0.245
	285.50	287.00	D004817	1.50	0.155		0.155
	287.00	288.50	D004819	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	288.50	290.00	D004820	1.50	0.008		0.008
	290.00	291.50	D004821	1.50	0.010		0.010
	291.50	293.00	D004822	1.50	0.056		0.056
	293.00	294.50	D004823	1.50	0.740		0.740
	294.50	296.00	D004824	1.50	0.008		0.008
	296.00	297.50	D004825	1.50	0.013		0.013
	297.50	298.50	D004826	1.00	0.012		0.012
	298.50	299.50	D004827	1.00	<0.005		0.001
	299.50	301.00	D004829	1.50	0.215		0.215
	301.00	302.50	D004830	1.50	0.040		0.040
	302.50	303.60	D004831	1.10	0.360		0.360
	303.60	305.00	D004832	1.40	0.451		0.451
	305.00	306.50	D004833	1.50	0.477		0.477
	306.50	308.00	D004834	1.50	0.163		0.163
	308.00	309.50	D004836	1.50	0.312		0.312
	309.50	311.00	D004837	1.50	1.195		1.195
	311.00	312.50	D004839	1.50	1.135		1.135
	312.50	314.00	D004840	1.50	0.142		0.142
	314.00	315.50	D004841	1.50	0.291		0.291
	315.50	317.00	D004842	1.50	0.117		0.117
	317.00	318.50	D004843	1.50	0.080		0.080
	318.50	320.00	D004844	1.50	0.005		0.005
	320.00	321.50	D004845	1.50	0.160		0.160
	321.50	323.00	D004846	1.50	0.011		0.011
	323.00	324.50	D004847	1.50	0.006		0.006
	324.50	326.00	D004849	1.50	0.006		0.006
	326.00	327.50	D004850	1.50	<0.005		0.001
	327.50	329.00	D004851	1.50	<0.005		0.001
	329.00	330.50	D004852	1.50	0.006		0.006
	330.50	332.00	D004853	1.50	0.008		0.008
	332.00	333.50	D004854	1.50	0.093		0.093
	333.50	335.00	D004855	1.50	0.033		0.033
	335.00	336.50	D004856	1.50	0.740		0.740

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	336.50	338.00	D004857	1.50	0.524		0.524
	338.00	339.50	D004859	1.50	0.016		0.016
	339.50	341.00	D004860	1.50	0.037		0.037
	341.00	342.50	D004861	1.50	0.087		0.087
	342.50	344.00	D004862	1.50	0.043		0.043
	344.00	345.50	D004863	1.50	0.027		0.027
	345.50	347.00	D004864	1.50	0.077		0.077
	347.00	348.50	D004865	1.50	0.074		0.074
	348.50	350.00	D004866	1.50	0.029		0.029
	350.00	351.50	D004867	1.50	<0.005		0.001
	351.50	353.00	D004869	1.50	0.013		0.013
	353.00	354.50	D004870	1.50	<0.005		0.001
	354.50	356.00	D004871	1.50	0.008		0.008
	356.00	357.50	D004872	1.50	<0.005		0.001
	357.50	359.00	D004873	1.50	0.014		0.014
	359.00	360.50	D004874	1.50	<0.005		0.001
	360.50	362.00	D004876	1.50	<0.005		0.001
	362.00	363.50	D004877	1.50	<0.005		0.001
	363.50	365.00	D004879	1.50	<0.005		0.001
	365.00	366.50	D004880	1.50	<0.005		0.001
	366.50	368.00	D004881	1.50	<0.005		0.001
	368.00	369.50	D004882	1.50	<0.005		0.001
	369.50	371.00	D004883	1.50	0.005		0.005
	371.00	372.00	D004884	1.00	<0.005		0.001
	372.00	372.90	D004885	0.90	0.005		0.005
	372.90	373.90	D004886	1.00	0.632		0.632
	373.90	375.00	D004887	1.10	0.006		0.006
	375.00	376.50	D004889	1.50	0.023		0.023
	376.50	378.00	D004890	1.50	<0.005		0.001
	378.00	379.50	D004891	1.50	<0.005		0.001
	379.50	381.00	D004892	1.50	<0.005		0.001
	381.00	382.50	D004893	1.50	0.006		0.006
	382.50	384.00	D004894	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			384.00	385.50	D004895	1.50	<0.005		0.001
			385.50	387.00	D004896	1.50	<0.005		0.001
			387.00	388.50	D004897	1.50	<0.005		0.001
			388.50	390.00	D004899	1.50	<0.005		0.001
			390.00	391.50	D004900	1.50	<0.005		0.001
			391.50	393.00	D004901	1.50	<0.005		0.001
			393.00	394.50	D004902	1.50	<0.005		0.001
			394.50	396.00	D004903	1.50	<0.005		0.001
			396.00	397.50	D004904	1.50	<0.005		0.001
			397.50	399.00	D004905	1.50	<0.005		0.001
			399.00	400.50	D004906	1.50	<0.005		0.001
			400.50	402.00	D004907	1.50	1.100		1.100
			402.00	403.50	D004909	1.50	1.375		1.375
			403.50	405.00	D004910	1.50	0.262		0.262
			405.00	406.50	D004911	1.50	<0.005		0.001
			406.50	408.00	D004912	1.50	0.006		0.006
			408.00	409.50	D004913	1.50	0.458		0.458
			409.50	411.00	D004914	1.50	0.202		0.202
			411.00	412.50	D004916	1.50	0.009		0.009
			412.50	413.80	D004917	1.30	0.365		0.365
413.80	414.80	SI05; CB03; CH <b>Silicifié 5; Carbonaté 3; Chloriteux</b>	413.80	414.80	D004919	1.00	1.150		1.150
414.80	440.00	BA; MAS <b>Basalte 50*; Massive</b> localement altéré en silice, qlq amygdules, passage légèrement cisailé, carbonâtes, chlorite, PY fine diss	414.80	416.50	D004920	1.70	2.560		2.560
			416.50	418.00	D004921	1.50	5.750		5.750
			418.00	419.50	D004922	1.50	0.845		0.845
			419.50	421.00	D004923	1.50	0.021		0.021
			421.00	422.50	D004924	1.50	0.015		0.015
			422.50	424.00	D004925	1.50	0.018		0.018
			424.00	425.20	D004926	1.20	1.060		1.060
			425.20	426.20	D004927	1.00	0.079		0.079
426.20	427.00	SI05; CB06 <b>Silicifié 5; Carbonaté 6</b>	426.20	427.00	D004929	0.80	>10.0	22.50	22.500
			427.00	428.50	D004930	1.50	0.058		0.058
			428.50	430.00	D004931	1.50	0.037		0.037

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	430.00	431.50	D004932	1.50	0.119		0.119
	431.50	433.00	D004933	1.50	<0.005		0.001
	433.00	434.50	D004934	1.50	0.005		0.005
	434.50	436.00	D004935	1.50	0.009		0.009
	436.00	437.50	D004936	1.50	<0.005		0.001
	437.50	439.00	D004937	1.50	0.006		0.006
	439.00	440.00	D004939	1.00	0.006		0.006
<p>440.00 Fin du sondage            Nombre d'échantillons : 299            Nombre d'échantillons QAQC : 42            Longueur totale échantillonnée : 438.60</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.50	15.00	D004608	D004607	1.50	<0.005	0.001
26.00	26.00	D004618	J	0.00	0.757	0.757
39.50	41.00	D004628	D004627	1.50	<0.005	0.001
48.50	48.50	D004635	M1	0.00	<0.005	0.001
51.50	51.50	D004638	K	0.00	1.150	1.150
65.00	66.50	D004648	D004647	1.50	<0.005	0.001
78.50	78.50	D004658	L	0.00	2.200	2.200
92.00	93.50	D004668	D004667	1.50	0.007	0.007
100.00	100.00	D004675	M1	0.00	<0.005	0.001
103.00	103.00	D004678	M	0.00	3.060	3.060
116.00	117.50	D004688	D004687	1.50	0.007	0.007
129.50	129.50	D004698	J	0.00	0.771	0.771
143.00	144.50	D004708	D004707	1.50	<0.005	0.001
152.00	152.00	D004715	M1	0.00	<0.005	0.001
155.00	155.00	D004718	K	0.00	1.035	1.035
168.50	170.00	D004728	D004727	1.50	0.006	0.006
182.00	182.00	D004738	L	0.00	2.180	2.180
195.50	197.00	D004748	D004747	1.50	0.024	0.024
203.00	203.00	D004755	M1	0.00	0.007	0.007
206.00	206.00	D004758	M	0.00	3.020	3.020
219.50	221.00	D004768	D004767	1.50	<0.005	0.001
233.00	233.00	D004778	J	0.00	0.756	0.756
246.50	248.00	D004788	D004787	1.50	0.009	0.009
255.50	255.50	D004795	M1	0.00	<0.005	0.001
258.50	258.50	D004798	K	0.00	1.050	1.050
272.00	273.50	D004808	D004807	1.50	0.031	0.031
285.50	285.50	D004818	L	0.00	2.110	2.110
298.50	299.50	D004828	D004827	1.00	<0.005	0.001
306.50	306.50	D004835	M1	0.00	<0.005	0.001
309.50	309.50	D004838	K	0.00	1.030	1.030
323.00	324.50	D004848	D004847	1.50	0.012	0.012
336.50	336.50	D004858	L	0.00	2.100	2.100
350.00	351.50	D004868	D004867	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
359.00	359.00	D004875	M1	0.00	<0.005	0.001
362.00	362.00	D004878	M	0.00	2.470	2.470
373.90	375.00	D004888	D004887	1.10	<0.005	0.001
387.00	387.00	D004898	J	0.00	0.800	0.800
400.50	402.00	D004908	D004907	1.50	0.958	0.958
409.50	409.50	D004915	M1	0.00	<0.005	0.001
412.50	412.50	D004918	K	0.00	0.935	0.935
425.20	426.20	D004928	D004927	1.00	0.064	0.064
437.50	437.50	D004938	L	0.00	1.555	1.555

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-186**

Titre minier :

Section :                      631200

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    Guy Gbaguidi

Lot :

Du :                              2010-04-21

Date de description :

Au :                              2010-04-23

Collet

UTM

Azimut :                      0.00°  
 Plongée :                    -55.00°  
 Longueur :                  299.00 m

Est	631 200.6
Nord	5 374 430.6
Élévation	304.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	357.80°	-55.20°	Non
Reflex	5.00	359.50°	-55.20°	Non
Reflex	8.00	358.50°	-55.20°	Non
Reflex	11.00	357.50°	-55.20°	Non
Reflex	14.00	357.50°	-55.20°	Non
Reflex	17.00	356.90°	-55.10°	Non
Reflex	20.00	357.30°	-55.10°	Non
Reflex	23.00	357.50°	-55.10°	Non
Reflex	26.00	357.60°	-55.10°	Non
Reflex	29.00	358.70°	-55.10°	Non
Reflex	32.00	358.60°	-55.10°	Non
Reflex	35.00	356.90°	-55.10°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.40°	-55.10°	Non
Reflex	41.00	358.30°	-55.00°	Non
Reflex	44.00	357.70°	-55.10°	Non
Reflex	47.00	356.70°	-55.00°	Non
Reflex	50.00	358.20°	-55.00°	Non
Reflex	53.00	357.90°	-55.00°	Non
Reflex	56.00	358.30°	-55.00°	Non
Reflex	59.00	358.00°	-54.90°	Non
Reflex	62.00	357.80°	-54.90°	Non
Reflex	65.00	358.00°	-54.90°	Non
Reflex	68.00	358.00°	-54.90°	Non
Reflex	71.00	358.10°	-54.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	358.40°	-54.80°	Non	Reflex	173.00	0.80°	-53.70°	Non
Reflex	77.00	358.50°	-54.80°	Non	Reflex	176.00	1.60°	-53.70°	Non
Reflex	80.00	358.40°	-54.70°	Non	Reflex	179.00	2.90°	-53.70°	Oui
Reflex	83.00	359.20°	-54.70°	Non	Reflex	182.00	1.10°	-53.70°	Non
Reflex	86.00	358.90°	-54.70°	Non	Reflex	185.00	0.60°	-53.70°	Non
Reflex	89.00	358.80°	-54.70°	Non	Reflex	188.00	0.70°	-53.70°	Non
Reflex	92.00	357.70°	-54.70°	Non	Reflex	191.00	0.80°	-53.70°	Non
Reflex	95.00	358.80°	-54.60°	Non	Reflex	194.00	0.80°	-53.70°	Non
Reflex	98.00	358.90°	-54.60°	Non	Reflex	197.00	0.80°	-53.60°	Non
Reflex	101.00	358.70°	-54.60°	Non	Reflex	200.00	1.00°	-53.70°	Non
Reflex	104.00	359.40°	-54.60°	Non	Reflex	203.00	1.20°	-53.60°	Non
Reflex	107.00	358.50°	-54.50°	Non	Reflex	206.00	1.70°	-53.60°	Non
Reflex	110.00	359.60°	-54.50°	Non	Reflex	209.00	1.20°	-53.60°	Non
Reflex	113.00	359.40°	-54.50°	Non	Reflex	212.00	1.40°	-53.60°	Non
Reflex	116.00	359.20°	-54.40°	Non	Reflex	215.00	1.70°	-53.60°	Non
Reflex	119.00	359.80°	-54.40°	Non	Reflex	218.00	2.00°	-53.60°	Non
Reflex	122.00	359.80°	-54.30°	Non	Reflex	221.00	2.20°	-53.60°	Non
Reflex	125.00	359.70°	-54.30°	Non	Reflex	224.00	2.20°	-53.60°	Non
Reflex	128.00	359.70°	-54.20°	Non	Reflex	227.00	2.10°	-53.50°	Non
Reflex	131.00	360.00°	-54.20°	Non	Reflex	230.00	2.40°	-53.60°	Non
Reflex	134.00	0.10°	-54.00°	Non	Reflex	233.00	2.40°	-53.60°	Non
Reflex	137.00	0.10°	-53.90°	Non	Reflex	236.00	2.40°	-53.50°	Non
Reflex	140.00	0.00°	-53.90°	Non	Reflex	239.00	2.40°	-53.50°	Non
Reflex	143.00	0.60°	-53.90°	Non	Reflex	242.00	2.50°	-53.50°	Non
Reflex	146.00	0.40°	-53.90°	Non	Reflex	245.00	2.40°	-53.50°	Non
Reflex	149.00	0.00°	-53.80°	Non	Reflex	248.00	2.50°	-53.50°	Non
Reflex	152.00	0.30°	-53.70°	Non	Reflex	251.00	2.50°	-53.40°	Non
Reflex	155.00	0.70°	-53.70°	Non	Reflex	254.00	2.50°	-53.40°	Non
Reflex	158.00	3.10°	-53.70°	Oui	Reflex	257.00	2.60°	-53.40°	Non
Reflex	161.00	2.40°	-53.70°	Non	Reflex	260.00	2.50°	-53.30°	Non
Reflex	164.00	1.70°	-53.70°	Non	Reflex	263.00	2.60°	-53.30°	Non
Reflex	167.00	0.90°	-53.70°	Non	Reflex	266.00	2.70°	-53.40°	Non
Reflex	170.00	1.60°	-53.70°	Non	Reflex	269.00	2.90°	-53.30°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	2.90°	-53.40°	Non					
Reflex	275.00	3.00°	-53.40°	Non					
Reflex	278.00	3.30°	-53.40°	Non					
Reflex	281.00	3.30°	-53.50°	Non					
Reflex	284.00	2.90°	-53.50°	Non					
Reflex	287.00	2.90°	-53.50°	Non					
Reflex	290.00	3.00°	-53.50°	Non					
Reflex	293.00	2.80°	-53.70°	Non					
Reflex	296.00	3.00°	-53.70°	Non					
Reflex	299.00	3.00°	-53.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	218.60	SY; POR	0.00	1.50	D022250	1.50	0.005		0.005
		<b>Syénite 30°; Porphyrique</b>	1.50	3.00	D022251	1.50	0.006		0.006
		Syénite porphyrique hématisée, carbonatée et séricitisée.	3.00	4.50	D022252	1.50	0.005		0.005
			4.50	6.00	D022253	1.50	0.018		0.018
			6.00	7.50	D022254	1.50	0.005		0.005
			7.50	9.00	D022256	1.50	0.015		0.015
			9.00	10.50	D022257	1.50	0.019		0.019
			10.50	12.00	D022258	1.50	0.222		0.222
			12.00	13.50	D022259	1.50	0.203		0.203
			13.50	15.00	D022260	1.50	1.110		1.110
			15.00	16.50	D022261	1.50	0.067		0.067
			16.50	18.00	D022262	1.50	0.009		0.009
			18.00	19.50	D022263	1.50	0.032		0.032
			19.50	21.00	D022264	1.50	0.045		0.045
			21.00	22.50	D022266	1.50	0.017		0.017
			22.50	24.20	D022267	1.70	0.035		0.035
			24.20	25.60	D022268	1.40	0.036		0.036
			25.60	27.00	D022269	1.40	0.015		0.015
			27.00	28.50	D022270	1.50	0.022		0.022
			28.50	30.00	D022271	1.50	0.005		0.005
			30.00	31.50	D022272	1.50	0.006		0.006
			31.50	33.00	D022273	1.50	0.020		0.020
			33.00	34.50	D022274	1.50	<0.005		0.001
			34.50	36.00	D022276	1.50	0.007		0.007
			36.00	37.50	D022277	1.50	0.017		0.017
			37.50	39.00	D022278	1.50	0.005		0.005
			39.00	40.50	D022279	1.50	0.005		0.005
			40.50	42.00	D022281	1.50	0.011		0.011
			42.00	43.50	D022282	1.50	0.011		0.011
			43.50	45.00	D022283	1.50	0.005		0.005
			45.00	46.50	D022284	1.50	0.006		0.006
			46.50	48.00	D022286	1.50	0.011		0.011
			48.00	49.50	D022287	1.50	0.009		0.009



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.50	51.00	D022288	1.50	<0.005		0.001
	51.00	52.50	D022289	1.50	<0.005		0.001
	52.50	54.00	D022290	1.50	<0.005		0.001
	54.00	55.00	D022291	1.00	<0.005		0.001
	55.00	56.00	D022292	1.00	<0.005		0.001
	56.00	57.00	D022293	1.00	2.460		2.460
	57.00	58.50	D022294	1.50	<0.005		0.001
	58.50	60.00	D022296	1.50	0.044		0.044
	60.00	61.50	D022297	1.50	<0.005		0.001
	61.50	63.00	D022298	1.50	0.008		0.008
	63.00	64.50	D022299	1.50	<0.005		0.001
	64.50	66.00	D022300	1.50	<0.005		0.001
	66.00	67.00	D022301	1.00	<0.005		0.001
	67.00	68.50	D022302	1.50	<0.005		0.001
	68.50	70.00	D022303	1.50	0.052		0.052
	70.00	71.50	D022304	1.50	<0.005		0.001
	71.50	73.00	D022306	1.50	0.007		0.007
	73.00	74.50	D022307	1.50	0.067		0.067
	74.50	76.00	D022308	1.50	0.010		0.010
	76.00	77.50	D022309	1.50	0.011		0.011
	77.50	79.00	D022310	1.50	0.516		0.516
	79.00	80.50	D022311	1.50	0.005		0.005
	80.50	82.00	D022312	1.50	0.072		0.072
	82.00	83.50	D022313	1.50	0.015		0.015
	83.50	85.00	D022314	1.50	0.011		0.011
	85.00	86.50	D022316	1.50	0.052		0.052
	86.50	88.00	D022317	1.50	1.080		1.080
	88.00	89.50	D022318	1.50	0.344		0.344
	89.50	91.00	D022319	1.50	0.014		0.014
	91.00	92.50	D022321	1.50	0.009		0.009
	92.50	94.00	D022322	1.50	0.127		0.127
	94.00	95.50	D022323	1.50	0.022		0.022
	95.50	97.00	D022324	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	97.00	98.50	D022326	1.50	<0.005		0.001
	98.50	100.00	D022327	1.50	0.008		0.008
	100.00	101.50	D022328	1.50	<0.005		0.001
	101.50	103.00	D022329	1.50	0.011		0.011
	103.00	104.50	D022330	1.50	0.601		0.601
	104.50	106.00	D022331	1.50	0.079		0.079
	106.00	107.50	D022332	1.50	0.021		0.021
	107.50	109.00	D022333	1.50	0.208		0.208
	109.00	110.00	D022334	1.00	<0.005		0.001
	110.00	111.00	D022336	1.00	0.006		0.006
	111.00	112.30	D022337	1.30	1.420		1.420
	112.30	114.00	D022338	1.70	0.042		0.042
	114.00	115.50	D022339	1.50	0.018		0.018
	115.50	117.00	D022340	1.50	0.005		0.005
	117.00	118.50	D022341	1.50	0.005		0.005
	118.50	120.00	D022342	1.50	<0.005		0.001
	120.00	121.50	D022343	1.50	<0.005		0.001
	121.50	123.00	D022344	1.50	<0.005		0.001
	123.00	124.00	D022346	1.00	0.148		0.148
	124.00	125.50	D022347	1.50	0.247		0.247
	125.50	127.20	D022348	1.70	0.023		0.023
	127.20	128.90	D022349	1.70	<0.005		0.001
	128.90	130.50	D022350	1.60	0.053		0.053
	130.50	132.00	D022351	1.50	0.117		0.117
	132.00	133.50	D022352	1.50	1.370		1.370
	133.50	135.00	D022353	1.50	0.170		0.170
	135.00	136.50	D022354	1.50	0.473		0.473
	136.50	138.00	D022356	1.50	0.074		0.074
	138.00	139.50	D022357	1.50	0.009		0.009
	139.50	141.00	D022358	1.50	0.126		0.126
	141.00	142.50	D022359	1.50	0.075		0.075
	142.50	144.00	D022361	1.50	0.022		0.022
	144.00	145.50	D022362	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	145.50	147.00	D022363	1.50	0.397		0.397
	147.00	148.50	D022364	1.50	<0.005		0.001
	148.50	150.00	D022366	1.50	0.326		0.326
	150.00	151.50	D022367	1.50	0.027		0.027
	151.50	153.00	D022368	1.50	0.005		0.005
	153.00	154.50	D022369	1.50	0.024		0.024
	154.50	156.00	D022370	1.50	0.163		0.163
	156.00	157.50	D022371	1.50	0.011		0.011
	157.50	159.00	D022372	1.50	0.231		0.231
	159.00	160.50	D022373	1.50	0.007		0.007
	160.50	162.00	D022374	1.50	<0.005		0.001
	162.00	163.50	D022376	1.50	0.157		0.157
	163.50	165.00	D022377	1.50	0.027		0.027
	165.00	166.00	D022378	1.00	0.430		0.430
	166.00	167.30	D022379	1.30	0.701		0.701
	167.30	168.30	D022380	1.00	3.490		3.490
	168.30	169.70	D022381	1.40	2.650		2.650
	169.70	171.00	D022382	1.30	0.271		0.271
	171.00	172.50	D022383	1.50	0.114		0.114
	172.50	174.00	D022384	1.50	0.416		0.416
	174.00	175.50	D022386	1.50	0.269		0.269
	175.50	177.00	D022387	1.50	1.270		1.270
	177.00	178.50	D022388	1.50	1.810		1.810
	178.50	180.00	D022389	1.50	1.995		1.995
	180.00	181.50	D022390	1.50	0.963		0.963
	181.50	183.00	D022391	1.50	0.161		0.161
	183.00	184.50	D022392	1.50	0.069		0.069
	184.50	186.00	D022393	1.50	0.005		0.005
	186.00	187.70	D022394	1.70	0.352		0.352
	187.70	189.00	D022396	1.30	2.220		2.220
	189.00	190.50	D022397	1.50	3.500		3.500
	190.50	192.00	D022398	1.50	0.096		0.096
	192.00	193.50	D022399	1.50	0.087		0.087

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
218.60	234.00	BA; MAS <b>Basalte 20°; Roche massive</b> basalte massive localement amygdalair.	193.50	195.00	D022401	1.50	0.025		0.025			
			195.00	196.00	D022402	1.00	0.013		0.013			
			196.00	197.50	D022403	1.50	0.069		0.069			
			197.50	199.00	D022404	1.50	0.071		0.071			
			199.00	200.50	D022406	1.50	0.033		0.033			
			200.50	202.00	D022407	1.50	0.145		0.145			
			202.00	203.50	D022408	1.50	0.015		0.015			
			203.50	205.00	D022409	1.50	0.024		0.024			
			205.00	206.40	D022410	1.40	0.219		0.219			
			206.40	208.00	D022411	1.60	4.380		4.380			
			208.00	209.50	D022412	1.50	7.150		7.150			
			209.50	211.00	D022413	1.50	6.860		6.860			
			211.00	212.50	D022414	1.50	3.000		3.000			
			212.50	214.00	D022416	1.50	2.190		2.190			
			214.00	215.50	D022417	1.50	1.825		1.825			
			215.50	217.00	D022418	1.50	1.445		1.445			
			217.00	218.60	D022419	1.60	2.900		2.900			
			234.00	299.00	GA; MAS <b>Gabbro; Roche massive</b> Gabbro massive carbonaté.	218.60	220.00	D022420	1.40	1.300		1.300
						220.00	221.70	D022421	1.70	1.420		1.420
						221.70	223.00	D022422	1.30	1.245		1.245
223.00	224.50	D022423				1.50	0.619		0.619			
224.50	226.00	D022424				1.50	0.014		0.014			
226.00	227.50	D022426				1.50	0.007		0.007			
227.50	229.00	D022427				1.50	0.006		0.006			
229.00	230.00	D022428				1.00	0.013		0.013			
230.00	231.50	D022429				1.50	0.010		0.010			
231.50	232.60	D022430				1.10	0.007		0.007			
232.60	234.00	D022431				1.40	0.012		0.012			
234.00	235.50	D022432				1.50	0.045		0.045			
235.50	237.00	D022433				1.50	0.086		0.086			
237.00	238.50	D022434				1.50	0.326		0.326			
238.50	240.00	D022436				1.50	0.052		0.052			
240.00	240.90	D022437				0.90	0.252		0.252			

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	240.90	242.00	D022438	1.10	8.800		8.800	
	242.00	243.50	D022439	1.50	2.630		2.630	
	243.50	245.00	D022441	1.50	0.020		0.020	
	245.00	246.50	D022442	1.50	<0.005		0.001	
	246.50	248.00	D022443	1.50	<0.005		0.001	
	248.00	249.50	D022444	1.50	<0.005		0.001	
	249.50	251.00	D022446	1.50	0.014		0.014	
	251.00	252.50	D022447	1.50	<0.005		0.001	
	252.50	254.00	D022448	1.50	0.029		0.029	
	254.00	255.50	D022449	1.50	<0.005		0.001	
	255.50	257.00	D022450	1.50	<0.005		0.001	
	257.00	258.50	D022451	1.50	<0.005		0.001	
	258.50	260.00	D022452	1.50	<0.005		0.001	
	260.00	261.50	D022453	1.50	<0.005		0.001	
	261.50	263.00	D022454	1.50	<0.005		0.001	
262.00	284.00	FAI	263.00	264.50	D022456	1.50	<0.005	0.001
		<b>Faïlle</b>	264.50	266.00	D022457	1.50	<0.005	0.001
		Gabbro cisailé fortement carbonaté avec présence de boue de	266.00	267.00	D022458	1.00	<0.005	0.001
		faïlle.	267.00	268.50	D022459	1.50	<0.005	0.001
			268.50	270.00	D022460	1.50	<0.005	0.001
			270.00	271.50	D022461	1.50	<0.005	0.001
			271.50	273.00	D022462	1.50	<0.005	0.001
			273.00	274.50	D022463	1.50	<0.005	0.001
			274.50	276.00	D022464	1.50	<0.005	0.001
			276.00	277.50	D022466	1.50	<0.005	0.001
			277.50	279.00	D022467	1.50	<0.005	0.001
			279.00	280.50	D022468	1.50	<0.005	0.001
			280.50	282.00	D022469	1.50	<0.005	0.001
			282.00	283.30	D022470	1.30	<0.005	0.001
			284.00	285.50	D022471	1.50	<0.005	0.001
			285.50	287.00	D022472	1.50	<0.005	0.001
			287.00	288.50	D022473	1.50	<0.005	0.001
			288.50	290.00	D022474	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
289.00	294.50	FAI <b>Faille</b> Gaggro cisailé, fortement carbonaté avec présence de boue de faille.	290.00	291.50	D022476	1.50	<0.005		0.001
			291.50	293.00	D022477	1.50	<0.005		0.001
			293.00	294.50	D022478	1.50	<0.005		0.001
			294.50	296.00	D022479	1.50	<0.005		0.001
			296.00	297.50	D022481	1.50	<0.005		0.001
			297.50	299.00	D022482	1.50	<0.005		0.001
299.00	Fin du sondage Nombre d'échantillons : 204 Nombre d'échantillons QAQC : 29 Longueur totale échantillonnée : 298.30								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	6.00	D022255	L	0.00	2.240	2.240
19.50	21.00	D022265	D022264	1.50	0.035	0.035
33.00	33.00	D022275	M	0.00	2.910	2.910
39.00	39.00	D022280	M1	0.00	<0.005	0.001
45.00	46.50	D022285	D022284	1.50	<0.005	0.001
57.00	57.00	D022295	J	0.00	0.799	0.799
70.00	71.50	D022305	D022304	1.50	<0.005	0.001
83.50	83.50	D022315	K	0.00	0.984	0.984
89.50	89.50	D022320	M1	0.00	<0.005	0.001
95.50	97.00	D022325	D022324	1.50	0.006	0.006
109.00	109.00	D022335	J	0.00	0.765	0.765
121.50	123.00	D022345	D022344	1.50	<0.005	0.001
135.00	135.00	D022355	K	0.00	1.005	1.005
141.00	141.00	D022360	M1	0.00	0.006	0.006
147.00	148.50	D022365	D022364	1.50	0.012	0.012
160.50	160.50	D022375	L	0.00	2.100	2.100
172.50	174.00	D022385	D022384	1.50	0.406	0.406
186.00	186.00	D022395	M	0.00	2.750	2.750
192.00	192.00	D022400	M1	0.00	0.007	0.007
197.50	199.00	D022405	D022404	1.50	0.079	0.079
211.00	211.00	D022415	J	0.00	0.761	0.761
224.50	226.00	D022425	D022424	1.50	0.012	0.012
237.00	237.00	D022435	K	0.00	1.100	1.100
242.00	242.00	D022440	M1	0.00	0.021	0.021
248.00	249.50	D022445	D022444	1.50	<0.005	0.001
261.50	261.50	D022455	J	0.00	0.786	0.786
274.50	276.00	D022465	D022464	1.50	<0.005	0.001
288.50	288.50	D022475	K	0.00	1.040	1.040
294.50	294.50	D022480	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-187**

Titre minier :

Section :                      631200

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles.KAMTA

Lot :

Du :                              2010-04-23

Date de description :              2010-06-14

Au :                              2010-04-27

Collet

UTM

Azimut :                      180.00°

Plongée :                      -58.00°

Longueur :                      467.00 m

Est                              631 200.2

Nord                              5 374 431.1

Élévation                      305.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	178.80°	-58.50°	Non
Reflex	8.00	182.60°	-58.20°	Oui
Reflex	11.00	179.00°	-58.20°	Non
Reflex	14.00	181.20°	-57.70°	Non
Reflex	17.00	181.60°	-57.80°	Non
Reflex	20.00	182.40°	-57.80°	Non
Reflex	23.00	182.30°	-57.80°	Non
Reflex	26.00	182.80°	-57.90°	Non
Reflex	29.00	183.00°	-57.90°	Non
Reflex	32.00	182.60°	-58.00°	Non
Reflex	35.00	182.10°	-58.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	181.90°	-58.00°	Non
Reflex	41.00	182.00°	-58.00°	Non
Reflex	44.00	182.80°	-58.00°	Non
Reflex	47.00	181.40°	-58.00°	Non
Reflex	50.00	181.80°	-58.00°	Non
Reflex	53.00	182.40°	-58.00°	Non
Reflex	56.00	183.50°	-58.00°	Oui
Reflex	59.00	181.90°	-57.90°	Non
Reflex	62.00	181.40°	-58.10°	Non
Reflex	65.00	183.10°	-58.00°	Non
Reflex	68.00	183.50°	-57.90°	Non
Reflex	71.00	183.40°	-57.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	183.50°	-57.80°	Non
Reflex	77.00	183.40°	-57.80°	Non
Reflex	80.00	183.30°	-57.80°	Non
Reflex	83.00	183.50°	-57.80°	Non
Reflex	86.00	183.80°	-57.80°	Non
Reflex	89.00	183.90°	-57.80°	Non
Reflex	92.00	184.00°	-57.80°	Non
Reflex	95.00	184.30°	-57.80°	Non
Reflex	98.00	184.50°	-57.80°	Non
Reflex	101.00	184.80°	-57.90°	Non
Reflex	104.00	184.80°	-57.90°	Non
Reflex	107.00	185.00°	-57.80°	Non
Reflex	110.00	185.10°	-57.80°	Non
Reflex	113.00	185.20°	-57.80°	Non
Reflex	116.00	185.60°	-57.80°	Non
Reflex	119.00	185.10°	-57.80°	Non
Reflex	122.00	185.80°	-57.80°	Non
Reflex	125.00	185.10°	-57.80°	Non
Reflex	128.00	185.20°	-57.70°	Non
Reflex	131.00	185.30°	-57.80°	Non
Reflex	134.00	185.50°	-57.80°	Non
Reflex	137.00	185.60°	-57.70°	Non
Reflex	140.00	185.70°	-57.70°	Non
Reflex	143.00	185.80°	-57.70°	Non
Reflex	146.00	185.90°	-57.70°	Non
Reflex	149.00	186.20°	-57.60°	Non
Reflex	152.00	186.00°	-57.50°	Non
Reflex	155.00	186.10°	-57.50°	Non
Reflex	158.00	186.30°	-57.50°	Non
Reflex	161.00	186.50°	-57.40°	Non
Reflex	164.00	186.60°	-57.40°	Non
Reflex	167.00	186.60°	-57.30°	Non
Reflex	170.00	186.50°	-57.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	186.70°	-57.20°	Non
Reflex	176.00	186.90°	-57.20°	Non
Reflex	179.00	187.00°	-57.20°	Non
Reflex	182.00	187.00°	-57.10°	Non
Reflex	185.00	186.40°	-57.00°	Non
Reflex	188.00	187.20°	-57.00°	Non
Reflex	191.00	187.20°	-56.90°	Non
Reflex	194.00	187.10°	-56.80°	Non
Reflex	197.00	187.20°	-56.70°	Non
Reflex	200.00	187.20°	-56.60°	Non
Reflex	203.00	186.00°	-56.60°	Non
Reflex	206.00	187.50°	-56.50°	Non
Reflex	209.00	187.20°	-56.50°	Non
Reflex	212.00	187.20°	-56.50°	Non
Reflex	215.00	187.20°	-56.40°	Non
Reflex	218.00	187.00°	-56.30°	Non
Reflex	221.00	187.60°	-56.40°	Non
Reflex	224.00	188.00°	-56.30°	Non
Reflex	227.00	188.10°	-56.30°	Non
Reflex	230.00	188.50°	-56.30°	Non
Reflex	233.00	188.40°	-56.20°	Non
Reflex	236.00	189.60°	-56.10°	Non
Reflex	239.00	186.10°	-56.20°	Non
Reflex	242.00	188.10°	-56.10°	Non
Reflex	245.00	188.40°	-56.00°	Non
Reflex	248.00	188.70°	-56.00°	Non
Reflex	251.00	188.70°	-56.00°	Non
Reflex	254.00	188.70°	-56.00°	Non
Reflex	257.00	189.20°	-56.00°	Non
Reflex	260.00	188.90°	-56.00°	Non
Reflex	263.00	189.40°	-56.00°	Non
Reflex	266.00	189.40°	-56.00°	Non
Reflex	269.00	189.30°	-55.90°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	189.30°	-55.80°	Non	Reflex	371.00	191.90°	-54.60°	Non
Reflex	275.00	189.50°	-55.80°	Non	Reflex	374.00	191.90°	-54.70°	Non
Reflex	278.00	189.40°	-55.70°	Non	Reflex	377.00	192.00°	-54.50°	Non
Reflex	281.00	189.30°	-55.70°	Non	Reflex	380.00	191.90°	-54.40°	Non
Reflex	284.00	189.50°	-55.60°	Non	Reflex	383.00	192.00°	-54.40°	Non
Reflex	287.00	190.00°	-55.60°	Non	Reflex	386.00	192.00°	-54.40°	Non
Reflex	290.00	189.70°	-55.60°	Non	Reflex	389.00	192.10°	-54.40°	Non
Reflex	293.00	189.90°	-55.40°	Non	Reflex	392.00	192.20°	-54.30°	Non
Reflex	296.00	190.00°	-55.40°	Non	Reflex	395.00	192.20°	-54.30°	Non
Reflex	299.00	189.90°	-55.30°	Non	Reflex	398.00	192.50°	-54.30°	Non
Reflex	302.00	189.80°	-55.40°	Non	Reflex	401.00	192.50°	-54.30°	Non
Reflex	305.00	189.80°	-55.30°	Non	Reflex	404.00	192.70°	-54.30°	Non
Reflex	308.00	190.00°	-55.20°	Non	Reflex	407.00	193.20°	-54.20°	Non
Reflex	311.00	189.90°	-55.20°	Non	Reflex	410.00	192.40°	-54.20°	Non
Reflex	314.00	190.20°	-55.10°	Non	Reflex	413.00	192.80°	-54.10°	Non
Reflex	317.00	190.20°	-55.10°	Non	Reflex	416.00	192.70°	-54.00°	Non
Reflex	320.00	190.40°	-55.10°	Non	Reflex	419.00	192.70°	-54.00°	Non
Reflex	323.00	190.60°	-55.10°	Non	Reflex	422.00	192.40°	-54.10°	Non
Reflex	326.00	190.50°	-55.00°	Non	Reflex	425.00	192.50°	-54.00°	Non
Reflex	329.00	190.70°	-55.00°	Non	Reflex	428.00	192.40°	-54.00°	Non
Reflex	332.00	190.80°	-55.00°	Non	Reflex	431.00	192.50°	-53.90°	Non
Reflex	335.00	190.90°	-55.00°	Non	Reflex	434.00	192.50°	-53.90°	Non
Reflex	338.00	191.00°	-54.90°	Non	Reflex	437.00	192.50°	-53.80°	Non
Reflex	341.00	191.10°	-54.90°	Non	Reflex	440.00	192.80°	-53.80°	Non
Reflex	344.00	191.10°	-54.90°	Non	Reflex	443.00	193.10°	-53.80°	Non
Reflex	347.00	191.20°	-54.80°	Non	Reflex	446.00	193.10°	-53.70°	Non
Reflex	350.00	191.40°	-54.80°	Non	Reflex	449.00	193.30°	-53.70°	Non
Reflex	353.00	191.40°	-54.70°	Non	Reflex	452.00	193.10°	-53.60°	Non
Reflex	356.00	191.40°	-54.80°	Non	Reflex	455.00	193.00°	-53.50°	Non
Reflex	359.00	191.40°	-54.70°	Non	Reflex	458.00	193.10°	-53.50°	Non
Reflex	362.00	191.50°	-54.70°	Non	Reflex	461.00	193.20°	-53.40°	Non
Reflex	365.00	191.60°	-54.70°	Non	Reflex	464.00	193.20°	-53.40°	Non
Reflex	368.00	191.80°	-54.70°	Non	Reflex	467.00	193.30°	-53.30°	Non

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	97.60	SY; MAS; FIN; MTY <b>Syénite; Roche massive; Grains fins; Grains moyens</b> grenue moyen à fin, localement qlq phénocristaux de FP mm sub arrondi, localement altéré en calcite, hématisation, carbonâtes de fer oxydé, séricite, localement magnétique.PY irréglièrement diss	0.00	1.50	D027189	1.50	0.047		0.047
			1.50	3.00	D027190	1.50	0.050		0.050
			3.00	4.50	D027191	1.50	0.015		0.015
			4.50	6.00	D027192	1.50	0.011		0.011
			6.00	7.50	D027193	1.50	0.028		0.028
0.00	57.00	SY; POR; FIN; MOY <b>Syénite; Porphyrique; Grains fins; Grains moyens</b> phénocristaux de FP automorphe à sub arrondi 0.2-0.5 cm							
7.50	9.00	FRC <b>Fracturé</b> fragments mm- cm, localement joint à 30° ac	7.50	9.00	D027194	1.50	1.020		1.020
			9.00	10.50	D027195	1.50	0.036		0.036
			10.50	12.00	D027196	1.50	0.017		0.017
			12.00	13.50	D027197	1.50	0.009		0.009
			13.50	15.00	D027199	1.50	0.009		0.009
			15.00	16.50	D027200	1.50	0.013		0.013
			16.50	18.00	D027201	1.50	0.049		0.049
			18.00	19.50	D027202	1.50	0.006		0.006
			19.50	21.00	D027203	1.50	0.008		0.008
			21.00	22.50	D027204	1.50	0.024		0.024
			22.50	24.00	D027205	1.50	0.074		0.074
			24.00	25.50	D027206	1.50	0.012		0.012
			25.50	27.00	D027207	1.50	0.016		0.016
			27.00	28.50	D027209	1.50	0.088		0.088
			28.50	30.00	D027210	1.50	0.020		0.020
			30.00	31.50	D027211	1.50	<0.005		0.001
			31.50	33.00	D027212	1.50	0.009		0.009
			33.00	34.50	D027213	1.50	0.015		0.015
			34.50	36.00	D027214	1.50	0.011		0.011
			36.00	37.50	D027215	1.50	0.014		0.014
37.50	39.00	D027216	1.50	0.019		0.019			
39.00	40.50	D027217	1.50	0.046		0.046			
40.50	42.00	D027219	1.50	0.009		0.009			
42.00	43.50	D027220	1.50	0.038		0.038			
43.50	45.00	D027221	1.50	0.008		0.008			
45.00	46.50	D027222	1.50	0.005		0.005			

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			46.50	48.00	D027223	1.50		0.013		0.013
			48.00	49.50	D027224	1.50		0.054		0.054
			49.50	51.00	D027226	1.50		0.006		0.006
			51.00	52.50	D027227	1.50		0.006		0.006
			52.50	54.00	D027229	1.50		0.009		0.009
			54.00	55.50	D027230	1.50		0.014		0.014
			55.50	57.00	D027231	1.50		0.154		0.154
			57.00	58.50	D027232	1.50		0.068		0.068
			58.50	60.00	D027233	1.50		0.014		0.014
			60.00	61.50	D027234	1.50		0.021		0.021
			61.50	62.50	D027235	1.00		0.066		0.066
			62.50	63.50	D027236	1.00		0.138		0.138
			63.50	65.00	D027237	1.50		0.895		0.895
			65.00	66.50	D027239	1.50		0.633		0.633
			66.50	68.00	D027240	1.50		2.570		2.570
			68.00	69.50	D027241	1.50		6.120		6.120
			69.50	70.50	D027242	1.00		3.090		3.090
			70.50	71.50	D027243	1.00		1.995		1.995
71.50	75.50	SiO3; CB; SR <b>Silicifié 3; Carbonaté; Séricitique</b> brêchique à sub brêchique, altération en silice, chlorite, calcite et séricite, PY fine diss	71.50	73.00	D027244	1.50		1.065		1.065
			73.00	74.50	D027245	1.50		1.835		1.835
			74.50	75.50	D027246	1.00		1.475		1.475
			75.50	77.00	D027247	1.50		0.556		0.556
			77.00	78.50	D027249	1.50		0.254		0.254
			78.50	79.50	D027250	1.00		0.472		0.472
			79.50	81.00	D027251	1.50		1.235		1.235
			81.00	82.50	D027252	1.50		2.260		2.260
			82.50	84.00	D027253	1.50		0.555		0.555
			84.00	85.50	D027254	1.50		1.635		1.635
85.50	90.90	SY; FIN; BRC <b>Syénite; Grains fins; Brèche de coulée</b> légèrement altéré en silice brêchique à sub brêchique à fragments anguleux, PY fine diss	85.50	87.00	D027255	1.50		1.055		1.055
			87.00	88.50	D027256	1.50		2.570		2.570
			88.50	90.00	D027257	1.50		2.480		2.480
			90.00	91.00	D027259	1.00		4.850		4.850
			91.00	92.60	D027260	1.60		0.400		0.400

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
97.60	98.00	NR <b>Carotte perdue</b> grindée	92.60	94.00	D027261	1.40	0.120		0.120			
			94.00	95.50	D027262	1.50	0.019		0.019			
			95.50	96.60	D027263	1.10	0.353		0.353			
			96.60	97.60	D027264	1.00	0.156		0.156			
98.00	154.30	SY; MTY; FIN <b>Syénite; Grains moyens; Grains fins</b> grains moyen à fin, localement bréchifié, passage altéré en silice, cheveux 40-60° ac, SR++, CL++, HM++, PY fine irrég diss	98.00	99.50	D027266	1.50	0.012		0.012			
			99.50	101.00	D027267	1.50	0.432		0.432			
			101.00	102.50	D027269	1.50	0.006		0.006			
			102.50	104.00	D027270	1.50	0.017		0.017			
			104.00	105.50	D027271	1.50	<0.005		0.001			
			105.50	107.00	D027272	1.50	0.008		0.008			
			107.00	108.50	D027273	1.50	0.054		0.054			
			108.50	110.00	D027274	1.50	0.058		0.058			
			110.00	111.50	D027275	1.50	0.103		0.103			
			111.50	113.00	D027276	1.50	0.091		0.091			
			113.00	114.50	D027277	1.50	0.013		0.013			
			114.50	116.00	D027279	1.50	0.055		0.055			
			116.00	137.80	SY; POR <b>Syénite; Porphyrique</b> grenue à grains moyen, phénocristaux de FP automorphe ou sub arrondi, grossier 0.3-2 cm, HM+++, localement séricitisé	116.00	117.50	D027280	1.50	0.181		0.181
						117.50	119.00	D027281	1.50	0.244		0.244
119.00	120.50	D027282				1.50	0.711		0.711			
120.50	122.00	D027283				1.50	0.222		0.222			
122.00	123.50	D027284				1.50	0.220		0.220			
123.50	125.00	D027285				1.50	0.130		0.130			
125.00	126.50	D027286				1.50	1.220		1.220			
126.50	128.00	D027287				1.50	0.086		0.086			
128.00	129.50	D027289				1.50	0.013		0.013			
129.50	131.00	D027290				1.50	0.131		0.131			
131.00	132.50	D027291				1.50	0.014		0.014			
132.50	134.00	D027292	1.50	0.019		0.019						
134.00	135.50	D027293	1.50	0.013		0.013						
135.50	137.00	D027294	1.50	0.289		0.289						
137.00	138.50	D027295	1.50	0.076		0.076						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
154.30	161.00	BA; AMY; MAS <b>Basalte 70°; Amygdalaire; Roche massive</b> massive, amygdules de QZ et carbonâtes mm, veinules et veines carbonatés, cheveux chloritisés, CL+++ , HM+++ , PY automorphe et fine diss	138.50	140.00	D027296	1.50	0.008		0.008
			140.00	141.40	D027297	1.40	<0.005		0.001
			141.40	143.00	D027299	1.60	0.012		0.012
			143.00	144.50	D027300	1.50	0.005		0.005
			144.50	145.90	D027301	1.40	<0.005		0.001
			145.90	147.00	D027302	1.10	0.016		0.016
			147.00	148.50	D027303	1.50	<0.005		0.001
			148.50	150.00	D027304	1.50	0.017		0.017
			150.00	151.50	D027306	1.50	0.005		0.005
			151.50	153.00	D027307	1.50	0.008		0.008
			153.00	154.30	D027309	1.30	0.009		0.009
			154.30	155.50	D027310	1.20	0.010		0.010
			155.50	157.00	D027311	1.50	0.763		0.763
			157.00	158.50	D027312	1.50	0.833		0.833
161.00	176.90	SY; MAS; FIN <b>Syénite 60°; Roche massive; Grains fins</b> massive localement bréchique, hématisation séricitisation, passages à phénocristaux de FP sub automorphe, PY irrég diss	158.50	160.00	D027313	1.50	0.008		0.008
			160.00	161.00	D027314	1.00	0.006		0.006
			161.00	162.50	D027315	1.50	0.012		0.012
			162.50	164.00	D027316	1.50	<0.005		0.001
			164.00	165.50	D027317	1.50	0.019		0.019
			165.50	167.00	D027319	1.50	<0.005		0.001
			167.00	168.50	D027320	1.50	0.007		0.007
			168.50	170.00	D027321	1.50	<0.005		0.001
			170.00	171.50	D027322	1.50	0.022		0.022
			171.50	173.00	D027323	1.50	<0.005		0.001
			173.00	174.50	D027324	1.50	<0.005		0.001
			174.50	176.00	D027325	1.50	<0.005		0.001
			176.00	176.90	D027326	0.90	0.006		0.006
			176.90	202.00	BA; COU; AMY <b>Basalte 70°; Coussiné; Amygdalaire</b> massive, localement bréchifié, amygdules de QZ et carbonâtes mm-cm, cheveux chloritisés, hématisation, sericitisation, PY fine diss	176.90	178.50	D027327	1.60
178.50	180.00	D027329				1.50	2.940		2.940
180.00	181.50	D027330				1.50	0.033		0.033
181.50	183.00	D027331				1.50	0.009		0.009
183.00	184.50	D027332				1.50	<0.005		0.001
184.50	186.00	D027333				1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			186.00	187.50	D027334	1.50	<0.005		0.001
			187.50	189.00	D027335	1.50	0.006		0.006
			189.00	190.50	D027336	1.50	<0.005		0.001
			190.50	192.00	D027337	1.50	<0.005		0.001
			192.00	193.50	D027339	1.50	<0.005		0.001
			193.50	195.00	D027340	1.50	0.005		0.005
			195.00	196.50	D027341	1.50	0.097		0.097
			196.50	198.00	D027342	1.50	<0.005		0.001
			198.00	199.20	D027343	1.20	<0.005		0.001
			199.20	200.20	D027344	1.00	<0.005		0.001
			200.20	201.50	D027346	1.30	<0.005		0.001
			201.50	203.00	D027347	1.50	<0.005		0.001
202.00	206.80	SY; FIN	203.00	204.50	D027349	1.50	<0.005		0.001
		<b>Syénite 70°; Grains fins</b>	204.50	205.80	D027350	1.30	<0.005		0.001
		massive grenue, qlq phénocristaux de FP t carbonâtes, HM+++, SR++, PY fine diss	205.80	206.80	D027351	1.00	<0.005		0.001
206.80	208.80	BA; MAS; AMY	206.80	207.80	D027352	1.00	<0.005		0.001
		<b>Basalte 40°; Roche massive; Amygdalaire</b>	207.80	208.80	D027353	1.00	0.005		0.005
		localement sub bréchique,							
208.80	226.60	SY; MAS; FIN; MTY	208.80	210.00	D027354	1.20	<0.005		0.001
		<b>Syénite 40°; Roche massive; Grains fins; Grains moyens</b>	210.00	211.50	D027355	1.50	<0.005		0.001
		massive, grenue, localement sub bréchique, veines et veinules de QZ carbonaté, altération en calcite, SR++, CL+, HM+++ , PY fine irrég diss	211.50	213.00	D027356	1.50	<0.005		0.001
			213.00	214.00	D027357	1.00	<0.005		0.001
			214.00	215.50	D027359	1.50	<0.005		0.001
			215.50	217.00	D027360	1.50	<0.005		0.001
			217.00	218.50	D027361	1.50	<0.005		0.001
			218.50	220.00	D027362	1.50	<0.005		0.001
			220.00	221.50	D027363	1.50	<0.005		0.001
			221.50	223.00	D027364	1.50	<0.005		0.001
			223.00	224.50	D027365	1.50	<0.005		0.001
			224.50	225.60	D027366	1.10	<0.005		0.001
			225.60	226.60	D027367	1.00	<0.005		0.001
226.60	252.50	BA; MAS; AMY	226.60	228.00	D027369	1.40	0.007		0.007
		<b>Basalte 40°; Roche massive; Amygdalaire</b>	228.00	229.50	D027370	1.50	0.005		0.005
		massive, localement cisailé, amydules deQZ et carbonâte, altération							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
en séricite et chlorite, localement calcique, EP+, localement magnetique			229.50	231.00	D027371	1.50	<0.005		0.001
			231.00	232.50	D027372	1.50	0.007		0.007
			232.50	234.00	D027373	1.50	<0.005		0.001
			234.00	235.50	D027374	1.50	<0.005		0.001
			235.50	237.00	D027375	1.50	<0.005		0.001
			237.00	238.50	D027376	1.50	<0.005		0.001
			238.50	240.00	D027377	1.50	0.006		0.006
			240.00	241.50	D027379	1.50	<0.005		0.001
			241.50	243.00	D027380	1.50	<0.005		0.001
			243.00	244.50	D027381	1.50	<0.005		0.001
			244.50	246.00	D027382	1.50	0.300		0.300
			246.00	247.50	D027383	1.50	0.712		0.712
			247.50	249.00	D027384	1.50	0.872		0.872
			249.00	250.50	D027386	1.50	<0.005		0.001
			250.50	251.50	D027387	1.00	0.041		0.041
251.50	252.50	D027389	1.00	3.680		3.680			
252.50	259.80	SY; FIN <b>Syénite 79°; Grains fins</b> massive, altération en calcite et hématisation							
252.50	259.80	SY; POR <b>Syénite; Porphyrique</b> texture trachytique, phénocristaux de FP automorphe étiré et orienté 50-70° ac, HM+++; altération en calcite PY fine diss	252.50	254.00	D027390	1.50	0.035		0.035
			254.00	255.50	D027391	1.50	0.014		0.014
			255.50	257.00	D027392	1.50	0.491		0.491
			257.00	258.50	D027393	1.50	0.084		0.084
			258.50	259.80	D027394	1.30	0.074		0.074
259.80	302.70	BA; MAS; AMY <b>Basalte 50°; Roche massive; Amygdalaire</b> massive, amygdules de qz et carbonâtes, altération en sericite, chlorite et calcite	259.80	261.00	D027395	1.20	2.390		2.390
			261.00	262.50	D027396	1.50	0.023		0.023
			262.50	264.00	D027397	1.50	0.006		0.006
			264.00	265.50	D027399	1.50	0.014		0.014
			265.50	267.00	D027400	1.50	<0.005		0.001
			267.00	268.50	D027401	1.50	<0.005		0.001
			268.50	270.00	D027402	1.50	<0.005		0.001
			270.00	271.50	D027403	1.50	<0.005		0.001
			271.50	273.00	D027404	1.50	<0.005		0.001
			273.00	274.50	D027405	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
302.70	303.60	SY; POR; FIN <b>Syénite 50°; Porphyrique; Grains fins</b> grenue à phénocristaux orienté 30-50° ac( texture pseudo trachytique), lentilles de QZ carbonaté, veinules de QZ, HM+++ , oxydes de carbonâtes, EP+, CL++, SR+, PY fine	274.50	276.00	D027406	1.50	<0.005		0.001
			276.00	277.50	D027407	1.50	0.005		0.005
			277.50	279.00	D027409	1.50	<0.005		0.001
			279.00	280.50	D027410	1.50	0.005		0.005
			280.50	282.00	D027411	1.50	0.005		0.005
			282.00	283.50	D027412	1.50	<0.005		0.001
			283.50	285.00	D027413	1.50	0.149		0.149
			285.00	286.50	D027414	1.50	<0.005		0.001
			286.50	288.00	D027415	1.50	<0.005		0.001
			288.00	289.50	D027416	1.50	<0.005		0.001
			289.50	291.00	D027417	1.50	<0.005		0.001
			291.00	292.50	D027419	1.50	<0.005		0.001
			292.50	294.00	D027420	1.50	<0.005		0.001
			294.00	295.50	D027421	1.50	<0.005		0.001
			295.50	297.00	D027422	1.50	<0.005		0.001
			297.00	298.50	D027423	1.50	<0.005		0.001
			298.50	300.00	D027424	1.50	<0.005		0.001
			300.00	301.50	D027426	1.50	<0.005		0.001
			301.50	302.70	D027427	1.20	<0.005		0.001
			302.70	303.60	D027429	0.90	<0.005		0.001
303.60	310.30	BA; MAS; AMY <b>Basalte 40°; Roche massive; Amygdalaire</b> massive légèrement cisailé, altération en séricite et chlorite, oxydes de carbonâtes	303.60	305.00	D027430	1.40	<0.005		0.001
			305.00	306.00	D027431	1.00	<0.005		0.001
			306.00	307.50	D027432	1.50	<0.005		0.001
			307.50	309.00	D027433	1.50	0.091		0.091
			309.00	310.30	D027434	1.30	<0.005		0.001
310.30	326.50	TU; FIN; MTY <b>Tuf à blocs felsique 50°; Grains fins; Grains moyens</b> grains moyen à fin, localement bréchifié, fragments anguleux, passages d' intrusion de basaltique, veines sherteuses, cheveux 40-60° ac, CL++, HM++, séricite, amygdules, PY fine diss	310.30	311.50	D027435	1.20	0.013		0.013
			311.50	313.00	D027436	1.50	0.006		0.006
			313.00	314.50	D027437	1.50	<0.005		0.001
			314.50	316.00	D027439	1.50	<0.005		0.001
			316.00	317.50	D027440	1.50	0.097		0.097

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
326.50	338.30	BA; MAS; AMY <b>Basalte 30°; Roche massive; Amygdalaire</b> massive, amygdules, localement cisailé, cheveux chloritisé, localement lentille de QZ pY en amas, séricite et chlorite	317.50	319.00	D027441	1.50	<0.005		0.001
			319.00	320.50	D027442	1.50	<0.005		0.001
			320.50	322.00	D027443	1.50	<0.005		0.001
			322.00	323.50	D027444	1.50	<0.005		0.001
			323.50	325.00	D027445	1.50	<0.005		0.001
			325.00	326.50	D027446	1.50	0.009		0.009
			326.50	328.00	D027447	1.50	0.006		0.006
			328.00	329.50	D027449	1.50	<0.005		0.001
			329.50	331.00	D027450	1.50	<0.005		0.001
			331.00	332.50	D027451	1.50	<0.005		0.001
			332.50	334.00	D027452	1.50	<0.005		0.001
			334.00	335.50	D027453	1.50	<0.005		0.001
			335.50	337.00	D027454	1.50	0.007		0.007
			337.00	338.30	D027455	1.30	2.030		2.030
338.30	354.80	SY; MAS; FIN <b>Syénite 70°; Roche massive; Grains fins</b> grenue, localement altéré en silice, séricitisé et hématisé, passage de bassalte amygdalaire, PY fine diss	338.30	340.00	D027456	1.70	1.270		1.270
			340.00	341.50	D027457	1.50	0.110		0.110
			341.50	343.00	D027459	1.50	0.036		0.036
			343.00	344.50	D027460	1.50	<0.005		0.001
			344.50	346.00	D027461	1.50	<0.005		0.001
			346.00	347.50	D027462	1.50	0.981		0.981
			347.50	349.00	D027463	1.50	0.023		0.023
			349.00	350.50	D027464	1.50	0.102		0.102
			350.50	352.00	D027466	1.50	0.023		0.023
			352.00	353.50	D027467	1.50	0.872		0.872
354.80	357.30	TU; AMY <b>Tuf à blocs felsique 50°; Amygdalaire</b> légèrement cisailé, fragments anguleux, localement altéré en silice, veinules et veines de QZ, altération en séricite, hématite	354.80	356.30	D027470	1.50	0.059		0.059
			356.30	357.30	D027471	1.00	0.271		0.271
357.30	360.10	SY; MAS; FIN <b>Syénite 30°; Roche massive; Grains fins</b> grenue, sub bréchique, légèrement silicifié, veines de QZ carbonatée, cheveux 40-60° ac, SR+++ , CL++ , HM+	357.30	359.00	D027472	1.70	3.770		3.770
			359.00	360.10	D027473	1.10	0.030		0.030
360.10	368.20	BA; MAS; AMY <b>Basalte 50°; Roche massive; Amygdalaire</b>	360.10	361.50	D027474	1.40	0.056		0.056

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
368.20	369.50	TU; BRC <b>Tuf à blocs mafique 30°; Brèche de coulée</b> massive, fragments anguleux, séricitisé, CL+++; oxydes de carbonâtes	361.50	363.00	D027475	1.50	0.005		0.005
			363.00	364.50	D027476	1.50	<0.005		0.001
			364.50	366.00	D027477	1.50	<0.005		0.001
			366.00	367.20	D027479	1.20	<0.005		0.001
			367.20	368.20	D027480	1.00	<0.005		0.001
			368.20	369.50	D027481	1.30	<0.005		0.001
369.50	395.70	TU; LAM; COU <b>Tuf à cendre/lapillis 40°; Laminations parallèles; Coussiné</b> grains fins, litage, fragments anguleux, cristaux, felsique, moucheture verdâtre, litages, SR+++; CL++, irrég PY fine diss	369.50	371.00	D027482	1.50	<0.005		0.001
			371.00	372.50	D027483	1.50	<0.005		0.001
			372.50	374.00	D027484	1.50	<0.005		0.001
			374.00	375.50	D027485	1.50	0.149		0.149
			375.50	377.00	D027486	1.50	<0.005		0.001
			377.00	378.50	D027487	1.50	<0.005		0.001
			378.50	380.00	D027489	1.50	<0.005		0.001
			380.00	381.50	D027490	1.50	0.005		0.005
			381.50	383.00	D027491	1.50	<0.005		0.001
			383.00	384.50	D027492	1.50	<0.005		0.001
			384.50	386.00	D027493	1.50	<0.005		0.001
			386.00	387.50	D027494	1.50	0.006		0.006
			387.50	389.00	D027495	1.50	0.005		0.005
			389.00	390.50	D027496	1.50	<0.005		0.001
			390.50	392.00	D027497	1.50	<0.005		0.001
			392.00	393.50	D027499	1.50	<0.005		0.001
395.70	402.50	BA; MAS; AMY <b>Basalte 70°; Roche massive; Amygdalaire</b> massive légèrement blanchi, aspect localement cherteux, localement brêchique, intercalations de tuf chloritisé, amygdules de QZ, localement altéré en calcite, PY fine, arsénopyrite	395.70	397.00	D027502	1.30	0.070		0.070
			397.00	398.50	D027503	1.50	3.390		3.390
			398.50	400.00	D027504	1.50	0.017		0.017
			400.00	401.50	D027506	1.50	0.005		0.005
			401.50	402.50	D027507	1.00	<0.005		0.001
			402.50	411.60	TU; LAM <b>Tuf à cendre/lapillis 50°; Laminations parallèles</b>	402.50	404.00	D027509	1.50
404.00	405.50	D027510				1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		litage, localement bloc mafique, passage altéré en silice, fragments de QZ, SR+++, HM+++, passablement altéré en silice	405.50	407.00	D027511	1.50	0.005		0.005
			407.00	408.50	D027512	1.50	0.005		0.005
			408.50	410.00	D027513	1.50	0.005		0.005
			410.00	411.60	D027514	1.60	<0.005		0.001
411.60	414.80	SY; POR; FIN; MTY	411.60	413.00	D027515	1.40	0.007		0.007
		<b>Syénite 80°; Porphyrique; Grains fins; Grains moyens</b> phénocristaux de FP sub arrondi 0.2-0.5 mm, altération en calcite, hématisation	413.00	414.00	D027516	1.00	<0.005		0.001
			414.00	414.80	D027517	0.80	<0.005		0.001
414.80	454.80	TU; COU	414.80	416.00	D027519	1.20	<0.005		0.001
		<b>Tuf à cendre/lapillis 70°; Coussiné</b> localement alternance de niveaux fin et très fin, fragments anguleux, altération calcite, Séricite, chlorite, epidotes, localement amygdules de QZ mm, veines de QZ	416.00	417.50	D027520	1.50	0.017		0.017
			417.50	419.00	D027521	1.50	0.097		0.097
			419.00	420.50	D027522	1.50	<0.005		0.001
			420.50	422.00	D027523	1.50	<0.005		0.001
			422.00	423.50	D027524	1.50	<0.005		0.001
			423.50	425.00	D027525	1.50	<0.005		0.001
			425.00	426.50	D027526	1.50	<0.005		0.001
			426.50	428.00	D027527	1.50	<0.005		0.001
			428.00	429.50	D027529	1.50	<0.005		0.001
			429.50	431.00	D027530	1.50	<0.005		0.001
			431.00	432.50	D027531	1.50	0.005		0.005
			432.50	434.00	D027532	1.50	<0.005		0.001
			434.00	435.50	D027533	1.50	<0.005		0.001
			435.50	437.00	D027534	1.50	0.005		0.005
			437.00	438.50	D027535	1.50	0.244		0.244
			438.50	440.00	D027536	1.50	0.005		0.005
			440.00	441.50	D027537	1.50	0.007		0.007
			441.50	443.00	D027539	1.50	0.005		0.005
			443.00	444.50	D027540	1.50	0.005		0.005
			444.50	446.00	D027541	1.50	0.006		0.006
446.00	447.50	D027542	1.50	0.023		0.023			
447.50	449.00	D027543	1.50	0.005		0.005			
449.00	450.50	D027544	1.50	<0.005		0.001			
450.50	452.00	D027546	1.50	0.005		0.005			
452.00	453.50	D027547	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
454.80	467.00	GR; FIN; LAM  <b>Grès 50°; Grains fins; Laminations parallèles</b> localement massive à grains fin, litage et laminations, passage de graphite, SR++, BO++, SR+, PY en amas et fine diss	453.50	454.80	D027549	1.30	<0.005		0.001
			454.80	456.00	D027550	1.20	0.027		0.027
			456.00	457.50	D027551	1.50	0.007		0.007
			457.50	459.00	D027552	1.50	0.022		0.022
			459.00	460.50	D027553	1.50	0.007		0.007
			460.50	462.00	D027554	1.50	<0.005		0.001
			462.00	463.50	D027555	1.50	<0.005		0.001
			463.50	465.00	D027556	1.50	<0.005		0.001
			465.00	466.00	D027557	1.00	<0.005		0.001
			466.00	467.00	D027559	1.00	<0.005		0.001
467.00	Fin du sondage Nombre d'échantillons : 325 Nombre d'échantillons QAQC : 46 Longueur totale échantillonnée : 466.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.00	13.50	D027198	D027197	1.50	0.010	0.010
25.50	25.50	D027208	J	0.00	0.711	0.711
39.00	40.50	D027218	D027217	1.50	0.012	0.012
48.00	48.00	D027225	M1	0.00	<0.005	0.001
51.00	51.00	D027228	K	0.00	1.030	1.030
63.50	65.00	D027238	D027237	1.50	0.870	0.870
75.50	75.50	D027248	L	0.00	2.400	2.400
88.50	90.00	D027258	D027257	1.50	2.490	2.490
96.60	96.60	D027265	M1	0.00	<0.005	0.001
99.50	99.50	D027268	M	0.00	3.030	3.030
113.00	114.50	D027278	D027277	1.50	0.013	0.013
126.50	126.50	D027288	J	0.00	0.792	0.792
140.00	141.40	D027298	D027297	1.40	<0.005	0.001
148.50	148.50	D027305	M1	0.00	<0.005	0.001
151.50	151.50	D027308	K	0.00	1.055	1.055
164.00	165.50	D027318	D027317	1.50	0.007	0.007
176.90	176.90	D027328	L	0.00	2.120	2.120
190.50	192.00	D027338	D027337	1.50	<0.005	0.001
199.20	199.20	D027345	M1	0.00	<0.005	0.001
201.50	201.50	D027348	M	0.00	3.060	3.060
213.00	214.00	D027358	D027357	1.00	<0.005	0.001
225.60	225.60	D027368	J	0.00	0.731	0.731
238.50	240.00	D027378	D027377	1.50	0.006	0.006
247.50	247.50	D027385	M1	0.00	<0.005	0.001
250.50	250.50	D027388	K	0.00	1.085	1.085
262.50	264.00	D027398	D027397	1.50	0.005	0.005
276.00	276.00	D027408	L	0.00	2.120	2.120
289.50	291.00	D027418	D027417	1.50	<0.005	0.001
298.50	298.50	D027425	M1	0.00	<0.005	0.001
301.50	301.50	D027428	M	0.00	3.150	3.150
313.00	314.50	D027438	D027437	1.50	<0.005	0.001
326.50	326.50	D027448	J	0.00	0.741	0.741
340.00	341.50	D027458	D027457	1.50	0.099	0.099

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
349.00	349.00	D027465	M1	0.00	<0.005	0.001
352.00	352.00	D027468	K	0.00	0.957	0.957
364.50	366.00	D027478	D027477	1.50	<0.005	0.001
377.00	377.00	D027488	L	0.00	1.905	1.905
390.50	392.00	D027498	D027497	1.50	<0.005	0.001
398.50	398.50	D027505	M1	0.00	0.005	0.005
401.50	401.50	D027508	M	0.00	3.300	3.300
414.00	414.80	D027518	D027517	0.80	<0.005	0.001
426.50	426.50	D027528	J	0.00	0.739	0.739
440.00	441.50	D027538	D027537	1.50	0.007	0.007
449.00	449.00	D027545	M1	0.00	<0.005	0.001
452.00	452.00	D027548	K	0.00	1.175	1.175
465.00	466.00	D027558	D027557	1.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-188**

Titre minier :

Section :                      631000

Canton :

Niveau :

Rang :

Place de travail :

Foré par :              Bradley

Lot :

Décrit par :          David RUHARA

Du :                      2010-05-02

Date de description :

Au :                     2010-05-09

Collet

UTM

Azimut :                0.00°

Plongée :              -60.00°

Longueur :            479.00 m

Est                      631 000.2

Nord                    5 374 300.1

Élévation             311.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	3.10°	-59.40°	Non
Reflex	8.00	2.60°	-59.40°	Non
Reflex	11.00	3.20°	-59.40°	Non
Reflex	14.00	2.80°	-59.10°	Non
Reflex	17.00	2.40°	-58.80°	Non
Reflex	20.00	2.50°	-58.70°	Non
Reflex	23.00	2.20°	-58.50°	Non
Reflex	26.00	2.20°	-58.50°	Non
Reflex	29.00	2.30°	-58.40°	Non
Reflex	32.00	2.40°	-58.40°	Non
Reflex	35.00	2.60°	-58.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.20°	-58.30°	Non
Reflex	41.00	3.00°	-58.30°	Non
Reflex	44.00	2.30°	-58.30°	Non
Reflex	47.00	2.90°	-58.20°	Non
Reflex	50.00	3.20°	-58.10°	Non
Reflex	53.00	3.00°	-58.10°	Non
Reflex	56.00	3.00°	-58.10°	Non
Reflex	59.00	3.00°	-58.00°	Non
Reflex	62.00	3.10°	-58.00°	Non
Reflex	65.00	3.10°	-58.00°	Non
Reflex	68.00	3.00°	-57.90°	Non
Reflex	71.00	2.90°	-57.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.90°	-57.90°	Non	Reflex	173.00	5.40°	-57.70°	Oui
Reflex	77.00	3.00°	-57.90°	Non	Reflex	176.00	3.20°	-57.60°	Non
Reflex	80.00	3.00°	-57.70°	Non	Reflex	179.00	1.30°	-57.60°	Non
Reflex	83.00	3.00°	-57.70°	Non	Reflex	182.00	2.70°	-57.60°	Non
Reflex	86.00	3.10°	-57.80°	Non	Reflex	185.00	5.30°	-57.60°	Non
Reflex	89.00	3.10°	-57.80°	Non	Reflex	188.00	6.10°	-57.60°	Non
Reflex	92.00	3.20°	-57.80°	Non	Reflex	191.00	6.30°	-57.70°	Non
Reflex	95.00	3.20°	-57.90°	Non	Reflex	194.00	6.00°	-57.70°	Non
Reflex	98.00	3.30°	-57.90°	Non	Reflex	197.00	4.40°	-57.60°	Non
Reflex	101.00	3.50°	-57.90°	Non	Reflex	200.00	4.10°	-57.60°	Non
Reflex	104.00	3.30°	-57.90°	Non	Reflex	203.00	5.40°	-57.60°	Non
Reflex	107.00	3.20°	-57.90°	Non	Reflex	206.00	2.30°	-57.60°	Oui
Reflex	110.00	3.20°	-58.00°	Non	Reflex	209.00	3.20°	-57.50°	Non
Reflex	113.00	3.30°	-58.00°	Non	Reflex	212.00	3.40°	-57.50°	Non
Reflex	116.00	3.30°	-58.00°	Non	Reflex	215.00	3.40°	-57.40°	Non
Reflex	119.00	3.20°	-58.00°	Non	Reflex	218.00	3.70°	-57.40°	Non
Reflex	122.00	3.50°	-58.00°	Non	Reflex	221.00	4.30°	-57.40°	Non
Reflex	125.00	3.50°	-58.00°	Non	Reflex	224.00	4.60°	-57.30°	Non
Reflex	128.00	3.50°	-58.00°	Non	Reflex	227.00	4.80°	-57.20°	Non
Reflex	131.00	3.50°	-58.00°	Non	Reflex	230.00	5.30°	-57.10°	Non
Reflex	134.00	3.20°	-58.00°	Non	Reflex	233.00	5.80°	-57.10°	Non
Reflex	137.00	3.50°	-58.00°	Non	Reflex	236.00	4.90°	-56.90°	Oui
Reflex	140.00	3.60°	-57.90°	Non	Reflex	239.00	6.30°	-56.80°	Non
Reflex	143.00	3.60°	-57.90°	Non	Reflex	242.00	7.20°	-58.40°	Non
Reflex	146.00	3.60°	-57.80°	Non	Reflex	245.00	6.30°	-56.60°	Non
Reflex	149.00	3.60°	-57.80°	Non	Reflex	248.00	5.40°	-56.40°	Non
Reflex	152.00	3.40°	-57.80°	Non	Reflex	251.00	4.30°	-56.40°	Non
Reflex	155.00	3.20°	-57.80°	Non	Reflex	254.00	6.20°	-56.30°	Non
Reflex	158.00	3.10°	-57.70°	Non	Reflex	257.00	2.70°	-56.30°	Oui
Reflex	161.00	3.00°	-57.70°	Non	Reflex	260.00	6.00°	-56.40°	Non
Reflex	164.00	3.30°	-57.70°	Non	Reflex	263.00	5.80°	-56.40°	Non
Reflex	167.00	2.80°	-57.70°	Non	Reflex	266.00	6.30°	-56.40°	Non
Reflex	170.00	5.40°	-57.60°	Oui	Reflex	269.00	6.40°	-56.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	6.90°	-56.40°	Non	Reflex	371.00	8.40°	-55.50°	Non
Reflex	275.00	7.40°	-56.40°	Non	Reflex	374.00	8.30°	-55.50°	Non
Reflex	278.00	4.80°	-56.30°	Oui	Reflex	377.00	37.80°	-65.20°	Oui
Reflex	281.00	7.70°	-56.30°	Non	Reflex	380.00	6.90°	-55.40°	Non
Reflex	284.00	6.60°	-56.40°	Non	Reflex	383.00	7.90°	-55.40°	Non
Reflex	287.00	6.70°	-56.40°	Non	Reflex	386.00	5.70°	-55.40°	Non
Reflex	290.00	5.20°	-56.30°	Non	Reflex	389.00	4.50°	-55.30°	Non
Reflex	293.00	8.10°	-56.40°	Non	Reflex	392.00	9.00°	-55.30°	Non
Reflex	296.00	7.30°	-56.40°	Non	Reflex	395.00	9.60°	-55.30°	Non
Reflex	299.00	8.30°	-56.40°	Non	Reflex	398.00	7.50°	-55.30°	Non
Reflex	302.00	7.90°	-56.40°	Non	Reflex	401.00	6.60°	-55.30°	Non
Reflex	305.00	8.40°	-56.40°	Non	Reflex	404.00	9.90°	-55.30°	Non
Reflex	308.00	7.60°	-56.40°	Non	Reflex	407.00	10.30°	-55.40°	Oui
Reflex	311.00	8.10°	-56.40°	Non	Reflex	410.00	9.60°	-55.30°	Non
Reflex	314.00	7.80°	-56.40°	Non	Reflex	413.00	9.10°	-55.20°	Non
Reflex	317.00	8.80°	-56.40°	Non	Reflex	416.00	9.60°	-55.00°	Non
Reflex	320.00	8.70°	-56.30°	Non	Reflex	419.00	9.50°	-54.90°	Non
Reflex	323.00	8.70°	-56.30°	Non	Reflex	422.00	9.40°	-54.90°	Non
Reflex	326.00	7.20°	-56.30°	Non	Reflex	425.00	10.40°	-54.90°	Non
Reflex	329.00	7.00°	-56.20°	Non	Reflex	428.00	8.60°	-54.90°	Non
Reflex	332.00	7.50°	-56.20°	Non	Reflex	431.00	10.10°	-54.90°	Non
Reflex	335.00	7.40°	-56.20°	Non	Reflex	434.00	9.60°	-54.80°	Non
Reflex	338.00	11.00°	-56.20°	Oui	Reflex	437.00	8.20°	-54.80°	Non
Reflex	341.00	8.90°	-56.20°	Non	Reflex	440.00	10.00°	-54.80°	Non
Reflex	344.00	9.60°	-56.20°	Non	Reflex	443.00	9.30°	-54.80°	Non
Reflex	347.00	5.00°	-56.10°	Non	Reflex	446.00	10.80°	-54.80°	Non
Reflex	350.00	5.80°	-55.90°	Non	Reflex	449.00	10.50°	-54.70°	Non
Reflex	353.00	5.20°	-55.80°	Non	Reflex	452.00	10.00°	-54.70°	Non
Reflex	356.00	4.60°	-55.70°	Non	Reflex	455.00	9.30°	-54.70°	Non
Reflex	359.00	9.60°	-55.60°	Non	Reflex	458.00	11.60°	-54.70°	Oui
Reflex	362.00	9.00°	-55.60°	Non	Reflex	461.00	10.60°	-54.70°	Non
Reflex	365.00	9.10°	-55.60°	Non	Reflex	464.00	9.80°	-54.60°	Non
Reflex	368.00	8.70°	-55.60°	Non	Reflex	467.00	7.60°	-54.50°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	6.80°	-54.40°	Non					
Reflex	473.00	6.90°	-54.30°	Non					
Reflex	476.00	6.60°	-54.30°	Non					
Reflex	479.00	6.20°	-54.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT						
		<b>Mort-terrain</b>						
2.50	4.20	SY; FIN	2.50	4.20	D018056	1.70	0.496	0.496
		<b>Syénite; Grains fins</b>						
		Syénite à grains fins avec passage de qlq phénocristaux de felsdpath.						
4.20	67.90	BA; MAS; AMY	4.20	5.50	D018058	1.30	0.026	0.026
		<b>Basalte 65°; Roche massive; Amygdalaire</b>						
		Basalte massive avec passage amygdalaires, yeux de QZ et vacuoles.						
			5.50	7.00	D018059	1.50	0.007	0.007
			7.00	8.50	D018060	1.50	<0.005	0.001
			8.50	10.00	D018061	1.50	<0.005	0.001
			10.00	11.50	D018062	1.50	<0.005	0.001
			11.50	13.00	D018063	1.50	<0.005	0.001
			13.00	14.50	D018064	1.50	<0.005	0.001
			14.50	16.00	D018065	1.50	0.006	0.006
			16.00	17.50	D018066	1.50	<0.005	0.001
			17.50	19.00	D018068	1.50	<0.005	0.001
			19.00	20.50	D018069	1.50	<0.005	0.001
			20.50	22.00	D018070	1.50	<0.005	0.001
			22.00	23.50	D018071	1.50	<0.005	0.001
			23.50	25.00	D018072	1.50	<0.005	0.001
			25.00	26.50	D018073	1.50	<0.005	0.001
			26.50	28.00	D018074	1.50	<0.005	0.001
			28.00	29.50	D018075	1.50	<0.005	0.001
			29.50	31.00	D018076	1.50	<0.005	0.001
			31.00	32.50	D018078	1.50	0.005	0.005
			32.50	34.00	D018079	1.50	<0.005	0.001
			34.00	35.50	D018080	1.50	<0.005	0.001
			35.50	37.00	D018081	1.50	0.007	0.007
			37.00	38.50	D018083	1.50	<0.005	0.001
			38.50	40.00	D018084	1.50	0.005	0.005
			40.00	41.50	D018085	1.50	0.005	0.005
			41.50	43.00	D018086	1.50	<0.005	0.001
			43.00	44.50	D018088	1.50	0.005	0.005
			44.50	46.00	D018089	1.50	0.009	0.009
			46.00	47.50	D018090	1.50	0.009	0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
67.90	479.00	SY; FIN; POR <b>Syénite 55°; Grains fins; Porphyrique</b> Syénite à grains fins et porphyrique avec de phénocristaux fins Xmm à rarement grossiers Xcm.	47.50	49.00	D018091	1.50	0.616		0.616
			49.00	50.50	D018092	1.50	<0.005		0.001
			50.50	52.00	D018093	1.50	<0.005		0.001
			52.00	53.50	D018094	1.50	<0.005		0.001
			53.50	55.00	D018095	1.50	0.007		0.007
			55.00	56.50	D018096	1.50	0.007		0.007
			56.50	58.00	D018098	1.50	0.010		0.010
			58.00	59.50	D018099	1.50	1.230		1.230
			59.50	61.00	D018100	1.50	0.013		0.013
			61.00	62.50	D018101	1.50	0.007		0.007
			62.50	64.00	D018103	1.50	0.006		0.006
			64.00	65.50	D018104	1.50	<0.005		0.001
			65.50	67.00	D018105	1.50	0.005		0.005
			67.00	67.90	D018106	0.90	0.009		0.009
			67.90	69.50	D018108	1.60	0.034		0.034
			69.50	71.00	D018109	1.50	2.160		2.160
			71.00	72.50	D018110	1.50	0.110		0.110
			72.50	74.00	D018111	1.50	0.009		0.009
			74.00	75.50	D018112	1.50	0.005		0.005
			75.50	77.00	D018113	1.50	0.006		0.006
			77.00	78.50	D018114	1.50	0.018		0.018
			78.50	80.00	D018115	1.50	0.083		0.083
			80.00	81.50	D018116	1.50	0.116		0.116
			81.50	83.00	D018118	1.50	0.016		0.016
			83.00	84.50	D018119	1.50	0.043		0.043
			84.50	86.00	D018120	1.50	0.119		0.119
			86.00	87.50	D018121	1.50	0.201		0.201
			87.50	89.00	D018122	1.50	0.306		0.306
89.00	90.50	D018123	1.50	0.226		0.226			
90.50	92.00	D018124	1.50	0.163		0.163			
92.00	93.50	D018125	1.50	0.287		0.287			
93.50	95.00	D018126	1.50	0.458		0.458			
95.00	96.50	D018128	1.50	0.019		0.019			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	96.50	98.00	D018129	1.50	0.034		0.034
	98.00	99.50	D018130	1.50	0.366		0.366
	99.50	101.00	D018131	1.50	0.056		0.056
	101.00	102.50	D018132	1.50	0.012		0.012
	102.50	104.00	D018133	1.50	0.025		0.025
	104.00	105.50	D018134	1.50	0.076		0.076
	105.50	107.00	D018135	1.50	0.024		0.024
	107.00	108.50	D018136	1.50	0.138		0.138
	108.50	110.00	D018138	1.50	0.242		0.242
	110.00	111.50	D018139	1.50	0.066		0.066
	111.50	113.00	D018140	1.50	0.017		0.017
	113.00	114.50	D018141	1.50	0.021		0.021
	114.50	116.00	D018143	1.50	0.403		0.403
	116.00	117.50	D018144	1.50	0.205		0.205
	117.50	119.00	D018145	1.50	0.065		0.065
	119.00	120.50	D018146	1.50	0.008		0.008
	120.50	122.00	D018148	1.50	0.038		0.038
	122.00	123.50	D018149	1.50	0.012		0.012
	123.50	125.00	D018150	1.50	0.011		0.011
	125.00	126.50	D018151	1.50	0.027		0.027
	126.50	128.00	D018152	1.50	0.006		0.006
	128.00	129.50	D018153	1.50	<0.005		0.001
	129.50	131.00	D018154	1.50	0.008		0.008
	131.00	132.50	D018155	1.50	0.014		0.014
	132.50	134.00	D018156	1.50	0.006		0.006
	134.00	135.50	D018158	1.50	0.018		0.018
	135.50	137.00	D018159	1.50	0.008		0.008
	137.00	138.50	D018160	1.50	<0.005		0.001
	138.50	140.00	D018161	1.50	<0.005		0.001
	140.00	141.50	D018162	1.50	<0.005		0.001
	141.50	143.00	D018163	1.50	0.006		0.006
	143.00	144.50	D018164	1.50	0.006		0.006
	144.50	146.00	D018165	1.50	0.044		0.044

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	146.00	147.50	D018166	1.50	0.048		0.048
	147.50	149.00	D018168	1.50	0.136		0.136
	149.00	150.50	D018169	1.50	0.174		0.174
	150.50	152.00	D018170	1.50	0.084		0.084
	152.00	153.50	D018171	1.50	0.272		0.272
	153.50	155.00	D018172	1.50	0.039		0.039
	155.00	156.50	D018173	1.50	1.405		1.405
	156.50	158.00	D018174	1.50	0.192		0.192
	158.00	159.50	D018175	1.50	0.306		0.306
	159.50	161.00	D018176	1.50	<0.005		0.001
	161.00	162.50	D018178	1.50	0.005		0.005
	162.50	164.00	D018179	1.50	0.093		0.093
	164.00	165.50	D018180	1.50	0.282		0.282
	165.50	167.00	D018181	1.50	0.025		0.025
	167.00	168.50	D018183	1.50	0.044		0.044
	168.50	170.00	D018184	1.50	0.058		0.058
	170.00	171.50	D018185	1.50	0.073		0.073
	171.50	173.00	D018186	1.50	0.195		0.195
	173.00	174.50	D018188	1.50	0.154		0.154
	174.50	176.00	D018189	1.50	0.064		0.064
	176.00	177.50	D018190	1.50	0.056		0.056
	177.50	179.00	D018191	1.50	0.040		0.040
	179.00	180.50	D018192	1.50	0.048		0.048
	180.50	182.00	D018193	1.50	0.031		0.031
	182.00	183.50	D018194	1.50	0.169		0.169
	183.50	185.00	D018195	1.50	0.103		0.103
	185.00	186.50	D018196	1.50	0.014		0.014
	186.50	188.00	D018198	1.50	0.056		0.056
	188.00	189.50	D018199	1.50	0.094		0.094
	189.50	191.00	D018200	1.50	0.037		0.037
	191.00	192.50	D018201	1.50	0.016		0.016
	192.50	194.00	D018202	1.50	0.148		0.148
	194.00	195.50	D018203	1.50	0.123		0.123

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	195.50	197.00	D018204	1.50	0.062		0.062
	197.00	198.50	D018205	1.50	0.074		0.074
	198.50	200.00	D018206	1.50	0.508		0.508
	200.00	201.00	D018208	1.00	1.385		1.385
	201.00	202.00	D018209	1.00	0.563		0.563
	202.00	203.50	D018210	1.50	0.194		0.194
	203.50	205.00	D018211	1.50	0.030		0.030
	205.00	206.50	D018212	1.50	0.301		0.301
	206.50	208.00	D018213	1.50	0.010		0.010
	208.00	209.50	D018214	1.50	<0.005		0.001
	209.50	211.00	D018215	1.50	0.011		0.011
	211.00	212.50	D018216	1.50	0.006		0.006
	212.50	214.00	D018218	1.50	<0.005		0.001
	214.00	215.50	D018219	1.50	<0.005		0.001
	215.50	217.00	D018220	1.50	0.012		0.012
	217.00	218.50	D018221	1.50	0.080		0.080
	218.50	220.00	D018223	1.50	0.273		0.273
	220.00	221.50	D018224	1.50	0.064		0.064
	221.50	223.00	D018225	1.50	0.170		0.170
	223.00	224.50	D018226	1.50	0.026		0.026
	224.50	226.00	D018228	1.50	0.013		0.013
	226.00	227.50	D018229	1.50	<0.005		0.001
	227.50	229.00	D018230	1.50	0.032		0.032
	229.00	230.50	D018231	1.50	<0.005		0.001
	230.50	232.00	D018232	1.50	<0.005		0.001
	232.00	233.50	D018233	1.50	<0.005		0.001
	233.50	235.00	D018234	1.50	<0.005		0.001
	235.00	236.50	D018235	1.50	<0.005		0.001
	236.50	238.00	D018236	1.50	<0.005		0.001
	238.00	239.50	D018238	1.50	<0.005		0.001
	239.50	241.00	D018239	1.50	<0.005		0.001
	241.00	242.50	D018240	1.50	<0.005		0.001
	242.50	244.00	D018241	1.50	0.005		0.005



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	244.00	245.50	D018242	1.50	<0.005		0.001
	245.50	247.00	D018243	1.50	<0.005		0.001
	247.00	248.50	D018244	1.50	0.023		0.023
	248.50	250.00	D018245	1.50	<0.005		0.001
	250.00	251.50	D018246	1.50	<0.005		0.001
	251.50	253.00	D018248	1.50	0.235		0.235
	253.00	254.50	D018249	1.50	0.017		0.017
	254.50	256.00	D018250	1.50	<0.005		0.001
	256.00	257.50	D018251	1.50	0.014		0.014
	257.50	259.00	D018252	1.50	<0.005		0.001
	259.00	260.50	D018253	1.50	<0.005		0.001
	260.50	262.00	D018254	1.50	<0.005		0.001
	262.00	263.50	D018255	1.50	<0.005		0.001
	263.50	265.00	D018256	1.50	0.011		0.011
	265.00	266.50	D018258	1.50	<0.005		0.001
	266.50	268.00	D018259	1.50	0.010		0.010
	268.00	269.50	D018260	1.50	<0.005		0.001
	269.50	271.00	D018261	1.50	<0.005		0.001
	271.00	272.50	D018263	1.50	0.007		0.007
	272.50	274.00	D018264	1.50	0.008		0.008
	274.00	275.50	D018265	1.50	<0.005		0.001
	275.50	277.00	D018266	1.50	0.114		0.114
	277.00	278.50	D018268	1.50	<0.005		0.001
	278.50	280.00	D018269	1.50	<0.005		0.001
	280.00	281.50	D018270	1.50	0.005		0.005
	281.50	283.00	D018271	1.50	0.006		0.006
	283.00	284.50	D018272	1.50	<0.005		0.001
	284.50	286.00	D018273	1.50	<0.005		0.001
	286.00	287.50	D018274	1.50	<0.005		0.001
	287.50	289.00	D018275	1.50	<0.005		0.001
	289.00	290.50	D018276	1.50	<0.005		0.001
	290.50	292.00	D018278	1.50	<0.005		0.001
	292.00	293.50	D018279	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	293.50	295.00	D018280	1.50	<0.005		0.001
	295.00	296.50	D018281	1.50	<0.005		0.001
	296.50	298.00	D018282	1.50	<0.005		0.001
	298.00	299.50	D018283	1.50	<0.005		0.001
	299.50	301.00	D018284	1.50	<0.005		0.001
	301.00	302.50	D018285	1.50	<0.005		0.001
	302.50	304.00	D018286	1.50	<0.005		0.001
	304.00	305.50	D018288	1.50	<0.005		0.001
	305.50	307.00	D018289	1.50	<0.005		0.001
	307.00	308.50	D018290	1.50	0.007		0.007
	308.50	310.00	D018291	1.50	<0.005		0.001
	310.00	311.50	D018292	1.50	<0.005		0.001
	311.50	313.00	D018293	1.50	0.014		0.014
	313.00	314.50	D018294	1.50	0.009		0.009
	314.50	316.00	D018295	1.50	0.008		0.008
	316.00	317.50	D018296	1.50	<0.005		0.001
	317.50	319.00	D018298	1.50	<0.005		0.001
	319.00	320.50	D018299	1.50	<0.005		0.001
	320.50	322.00	D018300	1.50	<0.005		0.001
	322.00	323.50	D018301	1.50	0.205		0.205
	323.50	325.00	D018303	1.50	1.545		1.545
	325.00	326.50	D018304	1.50	0.067		0.067
	326.50	328.00	D018305	1.50	<0.005		0.001
	328.00	329.50	D018306	1.50	0.165		0.165
	329.50	331.00	D018308	1.50	1.025		1.025
	331.00	332.50	D018309	1.50	<0.005		0.001
	332.50	334.00	D018310	1.50	<0.005		0.001
	334.00	335.50	D018311	1.50	<0.005		0.001
	335.50	337.00	D018312	1.50	0.008		0.008
	337.00	338.50	D018313	1.50	0.011		0.011
	338.50	340.00	D018314	1.50	0.024		0.024
	340.00	341.50	D018315	1.50	0.016		0.016
	341.50	343.00	D018316	1.50	0.023		0.023

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	343.00	344.50	D018318	1.50	0.062		0.062
	344.50	346.00	D018319	1.50	0.010		0.010
	346.00	347.50	D018320	1.50	0.007		0.007
	347.50	349.00	D018321	1.50	0.011		0.011
	349.00	350.50	D018322	1.50	0.033		0.033
	350.50	352.00	D018323	1.50	0.106		0.106
	352.00	353.50	D018324	1.50	0.020		0.020
	353.50	355.00	D018325	1.50	0.168		0.168
	355.00	356.50	D018326	1.50	0.120		0.120
	356.50	358.00	D018328	1.50	0.136		0.136
	358.00	359.50	D018329	1.50	0.048		0.048
	359.50	361.00	D018330	1.50	0.029		0.029
	361.00	362.50	D018331	1.50	0.012		0.012
	362.50	364.00	D018332	1.50	0.007		0.007
	364.00	365.50	D018333	1.50	0.023		0.023
	365.50	367.00	D018334	1.50	0.223		0.223
	367.00	368.50	D018335	1.50	0.121		0.121
	368.50	370.00	D018336	1.50	0.017		0.017
	370.00	371.50	D018338	1.50	0.029		0.029
	371.50	373.00	D018339	1.50	0.016		0.016
	373.00	374.50	D018340	1.50	<0.005		0.001
	374.50	376.00	D018341	1.50	0.403		0.403
	376.00	377.50	D018343	1.50	0.011		0.011
	377.50	379.00	D018344	1.50	0.105		0.105
	379.00	380.50	D018345	1.50	0.015		0.015
	380.50	382.00	D018346	1.50	0.006		0.006
	382.00	383.50	D018348	1.50	0.134		0.134
	383.50	385.00	D018349	1.50	0.341		0.341
	385.00	386.50	D018350	1.50	0.057		0.057
	386.50	388.00	D018351	1.50	0.052		0.052
	388.00	389.50	D018352	1.50	0.010		0.010
	389.50	391.00	D018353	1.50	0.013		0.013
	391.00	392.50	D018354	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	392.50	394.00	D018355	1.50	<0.005		0.001
	394.00	395.50	D018356	1.50	<0.005		0.001
	395.50	397.00	D018358	1.50	<0.005		0.001
	397.00	398.50	D018359	1.50	<0.005		0.001
	398.50	400.00	D018360	1.50	0.008		0.008
	400.00	401.50	D018361	1.50	0.034		0.034
	401.50	403.00	D018362	1.50	0.038		0.038
	403.00	404.50	D018363	1.50	0.006		0.006
	404.50	406.00	D018364	1.50	0.007		0.007
	406.00	407.50	D018365	1.50	0.005		0.005
	407.50	409.00	D018366	1.50	0.066		0.066
	409.00	410.50	D018368	1.50	<0.005		0.001
	410.50	412.00	D018369	1.50	0.097		0.097
	412.00	413.50	D018370	1.50	0.086		0.086
	413.50	415.00	D018371	1.50	0.120		0.120
	415.00	416.50	D018372	1.50	0.135		0.135
	416.50	418.00	D018373	1.50	0.621		0.621
	418.00	419.50	D018374	1.50	0.103		0.103
	419.50	421.00	D018375	1.50	0.087		0.087
	421.00	422.50	D018376	1.50	0.133		0.133
	422.50	424.00	D018378	1.50	0.071		0.071
	424.00	425.50	D018379	1.50	0.088		0.088
	425.50	427.00	D018380	1.50	0.065		0.065
	427.00	428.50	D018381	1.50	0.158		0.158
	428.50	430.00	D018383	1.50	0.064		0.064
	430.00	431.50	D018384	1.50	0.088		0.088
	431.50	433.00	D018385	1.50	0.017		0.017
	433.00	434.50	D018386	1.50	0.072		0.072
	434.50	436.00	D018388	1.50	0.039		0.039
	436.00	437.50	D018389	1.50	0.091		0.091
	437.50	439.00	D018390	1.50	<0.005		0.001
	439.00	440.50	D018391	1.50	0.005		0.005
	440.50	442.00	D018392	1.50	0.300		0.300

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	442.00	443.50	D018393	1.50	0.122		0.122
	443.50	445.00	D018394	1.50	0.027		0.027
	445.00	446.50	D018395	1.50	0.063		0.063
	446.50	448.00	D018396	1.50	0.169		0.169
	448.00	449.50	D018398	1.50	1.685		1.685
	449.50	451.00	D018399	1.50	2.140		2.140
	451.00	452.50	D018400	1.50	1.165		1.165
	452.50	454.00	D018401	1.50	0.059		0.059
	454.00	455.50	D018402	1.50	0.115		0.115
	455.50	457.00	D018403	1.50	0.200		0.200
	457.00	458.50	D018404	1.50	0.081		0.081
	458.50	460.00	D018405	1.50	0.167		0.167
	460.00	461.50	D018406	1.50	0.066		0.066
	461.50	463.00	D018408	1.50	0.421		0.421
	463.00	464.50	D018409	1.50	0.718		0.718
	464.50	466.00	D018410	1.50	0.477		0.477
	466.00	467.50	D018411	1.50	0.146		0.146
	467.50	469.00	D018412	1.50	0.316		0.316
	469.00	470.50	D018413	1.50	0.421		0.421
	470.50	472.00	D018414	1.50	0.917		0.917
	472.00	473.50	D018415	1.50	1.280		1.280
	473.50	475.00	D018416	1.50	1.210		1.210
	475.00	476.50	D018418	1.50	0.670		0.670
	476.50	478.00	D018419	1.50	0.182		0.182
	478.00	479.00	D018420	1.00	0.092		0.092
479.00	Fin du sondage Nombre d'échantillons : 319 Nombre d'échantillons QAQC : 46 Longueur totale échantillonnée : 476.50						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
2.50	4.20	D018057	D018056	1.70	0.493	0.493
16.00	17.50	D018067	K	1.50	0.983	0.983
29.50	31.00	D018077	D018076	1.50	<0.005	0.001
35.50	37.00	D018082	M1	1.50	<0.005	0.001
41.50	43.00	D018087	L	1.50	2.170	2.170
55.00	56.50	D018097	D018096	1.50	0.007	0.007
61.00	62.50	D018102	M1	1.50	<0.005	0.001
67.00	67.90	D018107	J	0.90	0.764	0.764
80.00	81.50	D018117	D018116	1.50	0.109	0.109
93.50	95.00	D018127	K	1.50	1.035	1.035
107.00	108.50	D018137	D018136	1.50	0.302	0.302
113.00	114.50	D018142	M1	1.50	<0.005	0.001
119.00	120.50	D018147	L	1.50	2.500	2.500
132.50	134.00	D018157	D018156	1.50	0.005	0.005
146.00	147.50	D018167	M	1.50	3.390	3.390
159.50	161.00	D018177	D018176	1.50	0.005	0.005
165.50	167.00	D018182	M1	1.50	<0.005	0.001
171.50	173.00	D018187	J	1.50	0.779	0.779
185.00	186.50	D018197	D018196	1.50	0.015	0.015
198.50	200.00	D018207	K	1.50	1.080	1.080
211.00	212.50	D018217	D018216	1.50	0.006	0.006
217.00	218.50	D018222	M1	1.50	<0.005	0.001
223.00	224.50	D018227	L	1.50	2.400	2.400
236.50	238.00	D018237	D018236	1.50	0.008	0.008
250.00	251.00	D018247	M	1.00	3.200	3.200
263.50	265.00	D018257	D018256	1.50	0.006	0.006
269.50	271.00	D018262	M1	1.50	<0.005	0.001
275.50	277.00	D018267	J	1.50	0.653	0.653
289.00	290.50	D018277	D018276	1.50	<0.005	0.001
302.50	304.00	D018287	K	1.50	1.120	1.120
316.00	317.50	D018297	D018296	1.50	<0.005	0.001
322.00	323.50	D018302	M1	1.50	<0.005	0.001
328.00	329.50	D018307	L	1.50	2.120	2.120

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
341.50	343.00	D018317	D018316	1.50	0.020	0.020
355.00	356.50	D018327	M	1.50	2.970	2.970
368.50	370.00	D018337	D018336	1.50	0.013	0.013
374.50	376.00	D018342	M1	1.50	<0.005	0.001
380.50	382.00	D018347	J	1.50	0.800	0.800
394.00	395.50	D018357	D018356	1.50	<0.005	0.001
407.50	409.00	D018367	K	1.50	0.999	0.999
421.00	422.50	D018377	D018376	1.50	0.142	0.142
427.00	428.50	D018382	M1	1.50	<0.005	0.001
433.00	434.50	D018387	L	1.50	2.210	2.210
446.50	448.00	D018397	D018396	1.50	0.176	0.176
460.00	461.50	D018407	M	1.50	3.080	3.080
473.50	475.00	D018417	D018416	1.50	1.315	1.315





Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	359.80°	-58.20°	Oui	Reflex	179.00	4.80°	-58.10°	Non
Reflex	83.00	3.00°	-58.10°	Non	Reflex	182.00	4.70°	-58.10°	Non
Reflex	86.00	5.40°	-58.20°	Oui	Reflex	185.00	3.70°	-58.20°	Non
Reflex	89.00	2.80°	-58.20°	Non	Reflex	188.00	1.10°	-58.20°	Oui
Reflex	92.00	2.30°	-58.20°	Non	Reflex	191.00	4.60°	-58.20°	Non
Reflex	95.00	0.50°	-58.20°	Non	Reflex	194.00	4.20°	-58.30°	Non
Reflex	98.00	0.80°	-58.30°	Non	Reflex	197.00	4.50°	-58.30°	Non
Reflex	101.00	1.30°	-58.30°	Non	Reflex	200.00	2.60°	-58.30°	Oui
Reflex	104.00	1.50°	-58.30°	Non	Reflex	203.00	0.60°	-58.30°	Oui
Reflex	107.00	2.30°	-58.20°	Non	Reflex	206.00	4.00°	-58.40°	Non
Reflex	110.00	2.20°	-58.20°	Non	Reflex	209.00	3.30°	-58.30°	Non
Reflex	113.00	1.60°	-58.30°	Non	Reflex	212.00	2.40°	-58.40°	Non
Reflex	116.00	3.90°	-58.30°	Oui	Reflex	215.00	5.00°	-58.30°	Non
Reflex	119.00	0.80°	-58.30°	Non	Reflex	218.00	5.20°	-58.40°	Non
Reflex	122.00	3.00°	-58.30°	Oui	Reflex	221.00	3.30°	-58.40°	Non
Reflex	125.00	360.00°	-58.30°	Non	Reflex	224.00	3.40°	-58.50°	Non
Reflex	128.00	1.80°	-58.20°	Non	Reflex	227.00	3.00°	-58.50°	Non
Reflex	131.00	1.30°	-58.20°	Non	Reflex	230.00	2.90°	-58.50°	Non
Reflex	134.00	1.10°	-58.10°	Non	Reflex	233.00	3.30°	-58.50°	Non
Reflex	137.00	1.90°	-58.10°	Non	Reflex	236.00	4.30°	-58.60°	Non
Reflex	140.00	1.50°	-58.10°	Non	Reflex	239.00	4.20°	-58.60°	Non
Reflex	143.00	4.20°	-58.10°	Oui	Reflex	242.00	5.70°	-58.60°	Oui
Reflex	146.00	2.50°	-58.10°	Non	Reflex	245.00	3.20°	-58.60°	Non
Reflex	149.00	5.20°	-58.10°	Oui	Reflex	248.00	3.80°	-58.60°	Non
Reflex	152.00	3.00°	-58.00°	Non	Reflex	251.00	3.80°	-58.60°	Non
Reflex	155.00	3.10°	-58.10°	Non	Reflex	254.00	4.00°	-58.70°	Non
Reflex	158.00	4.50°	-58.10°	Non	Reflex	257.00	4.10°	-58.60°	Non
Reflex	161.00	4.00°	-58.00°	Non	Reflex	260.00	4.20°	-58.60°	Non
Reflex	164.00	0.90°	-58.00°	Oui	Reflex	263.00	4.20°	-58.70°	Non
Reflex	167.00	3.50°	-58.00°	Non	Reflex	266.00	4.20°	-58.70°	Non
Reflex	170.00	4.80°	-58.00°	Non	Reflex	269.00	4.30°	-58.70°	Non
Reflex	173.00	6.60°	-58.00°	Non	Reflex	272.00	4.40°	-58.80°	Non
Reflex	176.00	3.80°	-58.10°	Non	Reflex	275.00	4.50°	-58.80°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	278.00	4.90°	-58.80°	Non					
Reflex	281.00	4.70°	-58.80°	Non					
Reflex	284.00	4.70°	-58.70°	Non					
Reflex	287.00	4.80°	-58.70°	Non					
Reflex	290.00	4.70°	-58.60°	Non					
Reflex	293.00	5.10°	-58.70°	Non					
Reflex	296.00	3.90°	-58.60°	Oui					
Reflex	299.00	4.90°	-58.60°	Non					
Reflex	302.00	4.90°	-58.60°	Non					
Reflex	305.00	5.00°	-58.50°	Non					
Reflex	308.00	5.00°	-58.40°	Non					
Reflex	311.00	5.00°	-58.40°	Non					
Reflex	314.00	5.10°	-58.40°	Non					
Reflex	317.00	5.10°	-58.30°	Non					
Reflex	320.00	5.20°	-58.30°	Non					
Reflex	323.00	5.10°	-58.20°	Non					
Reflex	326.00	5.20°	-58.20°	Non					
Reflex	329.00	5.10°	-58.10°	Non					
Reflex	332.00	5.00°	-58.10°	Non					
Reflex	335.00	5.00°	-58.00°	Non					
Reflex	338.00	5.00°	-58.00°	Non					
Reflex	341.00	5.10°	-57.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	6.00	MT						
		<b>Mort-terrain</b>						
6.00	123.39	SY; POR; MAS	6.00	7.00	D015388	1.00	<0.005	0.001
		<b>Syénite; Porphyrique; Roche massive</b>	7.00	8.00	D015389	1.00	<0.005	0.001
		Syénite porphyrique hématisée, massive et de teinte variable.	8.00	9.50	D015390	1.50	<0.005	0.001
		Elle se présente surtout rosâtre, violacée, orange, violacée et parfois beige.	9.50	11.00	D015391	1.50	<0.005	0.001
		Elle se compose de porphyres de feldspaths (10-50%) xéno à idiomorphes et montrant souvent une zonation.	11.00	12.50	D015393	1.50	<0.005	0.001
		Ils varient de 1x1mm à 1x1cm en dimensions.	12.50	14.00	D015394	1.50	0.012	0.012
		La syénite est faiblement carbonatisée par endroits.	14.00	15.50	D015395	1.50	<0.005	0.001
		Par endroits, nous observons de nombreuses fractures occupées par des veinules d'albite-quartz-carbonates, disposées aléatoirement et s'entrecoupant. Elles sont surtout disposées entre 45°-90°ac et variant de 1-2mm à 1cm en épaisseur. Ce système forme parfois un stockwerk.	15.50	17.00	D015396	1.50	<0.005	0.001
		Les porphyres de feldspaths sont parfois zonés et révèlent souvent une teinte rosâtre (hématisation).	17.00	18.50	D015397	1.50	<0.005	0.001
		Faiblement magnétique par endroits.	18.50	20.00	D015398	1.50	<0.005	0.001
		Traces de pyrite disséminée en cubes fins.	20.00	21.50	D015399	1.50	0.186	0.186
			21.50	23.00	D015401	1.50	<0.005	0.001
			23.00	24.50	D015403	1.50	<0.005	0.001
			24.50	26.00	D015404	1.50	<0.005	0.001
			26.00	27.50	D015405	1.50	<0.005	0.001
			27.50	29.00	D015406	1.50	0.005	0.005
			29.00	30.50	D015407	1.50	<0.005	0.001
			30.50	32.00	D015408	1.50	0.007	0.007
			32.00	33.50	D015409	1.50	<0.005	0.001
			33.50	35.00	D015410	1.50	<0.005	0.001
			35.00	36.50	D015411	1.50	0.005	0.005
			36.50	38.00	D015413	1.50	<0.005	0.001
			38.00	39.50	D015414	1.50	<0.005	0.001
			39.50	41.00	D015415	1.50	<0.005	0.001
			41.00	42.50	D015416	1.50	<0.005	0.001
			42.50	44.00	D015417	1.50	<0.005	0.001
			44.00	45.50	D015418	1.50	<0.005	0.001
			45.50	47.00	D015419	1.50	<0.005	0.001
			47.00	48.50	D015420	1.50	<0.005	0.001
			48.50	50.00	D015421	1.50	<0.005	0.001
			50.00	51.50	D015423	1.50	0.012	0.012
			51.50	53.00	D015424	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
63.66	64.13	CIS <b>Cisaillement 65°</b> Cisaillement d'intensité moyenne à forte. Les porphyres de feldspaths sont étirés, chloritisés. La syénite est de teinte verdâtre, chloritisée et carbonatisée. Présence de veinules de sidérite (carbonates de fer).	53.00	54.50	D015425	1.50	0.007		0.007
			54.50	56.00	D015426	1.50	<0.005		0.001
			56.00	57.50	D015427	1.50	<0.005		0.001
			57.50	59.00	D015428	1.50	<0.005		0.001
			59.00	60.50	D015429	1.50	<0.005		0.001
			60.50	62.00	D015430	1.50	<0.005		0.001
			62.00	63.50	D015431	1.50	<0.005		0.001
			63.50	65.00	D015433	1.50	0.006		0.006
67.26	67.68	CIS <b>Cisaillement 50°</b> Cisaillement de forte intensité et ayant une épaisseur d'environ 20cm. La syénite est altérée, vert pâle, beige. Elle est carbonatisée et séricitisée.	65.00	66.50	D015434	1.50	<0.005		0.001
			66.50	68.00	D015435	1.50	0.064		0.064
			68.00	69.50	D015436	1.50	0.063		0.063
			69.50	71.00	D015437	1.50	0.081		0.081
			71.00	72.50	D015438	1.50	<0.005		0.001
			72.50	74.00	D015439	1.50	0.027		0.027
			74.00	75.50	D015441	1.50	<0.005		0.001
			75.50	77.00	D015443	1.50	<0.005		0.001
			77.00	78.50	D015444	1.50	0.010		0.010
			78.50	80.00	D015445	1.50	<0.005		0.001
			80.00	81.50	D015446	1.50	<0.005		0.001
			81.50	83.00	D015447	1.50	<0.005		0.001
			83.00	84.50	D015448	1.50	<0.005		0.001
			84.50	86.00	D015449	1.50	<0.005		0.001
			86.00	87.50	D015450	1.50	<0.005		0.001
			87.50	89.00	D015451	1.50	0.146		0.146
			89.00	90.50	D015453	1.50	<0.005		0.001
			90.50	92.00	D015454	1.50	<0.005		0.001
92.00	93.50	D015455	1.50	<0.005		0.001			
93.50	95.00	D015456	1.50	<0.005		0.001			
95.00	96.50	D015457	1.50	<0.005		0.001			
96.50	98.00	D015458	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
97.76	98.00	FAI <b>Faille 25°</b> Faille ayant environ 10cm en épaisseur Matériel graphytique avec des fragments de syénite sub-angulaires à angulaires.	98.00	99.50	D015459	1.50	<0.005		0.001
			99.50	101.00	D015460	1.50	0.063		0.063
			101.00	102.50	D015461	1.50	<0.005		0.001
			102.50	104.00	D015463	1.50	0.007		0.007
102.64	104.00	CIS <b>Cisaillement 30°</b> Cisaillement d'intensité moyenne à forte. La syénite est de teinte vert pâle. Elle est séricitisée, chloritisée et carbonatisée. Les porphyres de feldspaths sont étirés, chloritisés.	104.00	105.50	D015464	1.50	0.018		0.018
			105.50	107.00	D015465	1.50	<0.005		0.001
			107.00	108.50	D015466	1.50	<0.005		0.001
			108.50	110.00	D015467	1.50	<0.005		0.001
			110.00	111.50	D015468	1.50	<0.005		0.001
			111.50	113.00	D015469	1.50	<0.005		0.001
			113.00	114.50	D015470	1.50	<0.005		0.001
			114.50	116.00	D015471	1.50	<0.005		0.001
			116.00	117.50	D015473	1.50	<0.005		0.001
			117.50	119.00	D015474	1.50	0.010		0.010
			119.00	120.50	D015475	1.50	<0.005		0.001
123.39	135.74	SY; FIN <b>Syénite 35°; Grains fins</b> Syénite altérée et déformée. Elle est affectée par un cisaillement d'intensité moyenne à forte. La schistosité se retrouve entre 15°-25°ac, et parfois selon l'ac. Sa teinte est surtout verdâtre et parfois rosâtre et beige. Elle est fortement chloritisée, séricitisée et carbonatisée par endroits. Parfois hématisée. La texture porphyrique est très peu évidente. Nous observons des taches de chlorite de forme allongée, qui peuvent être des porphyres de feldspaths altérés et déformés. Nous observons un système de veinules d'albite-carbonates, discontinues, déformées et disposées selon la déformation. Elles varient de 1-3mm en épaisseur. Présence d'un système de veinules de quartz-carbonates-chlorite et peut-être tourmaline, gris foncé et grisâtre. Elles sont disposées entre 0°-30°ac et varient de 1-10cm en épaisseur. Ce système est parfois minéralisé en pyrite fine et représente environ 10% du volume de la carotte. Présence de pyrite dispersée par endroits, en cubes fins à moyens.	120.50	122.00	D015476	1.50	<0.005		0.001
			122.00	123.39	D015477	1.39	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
123.39	135.74	<p>CIS</p> <p><b>Cisaillement 20°</b></p> <p>Bon cisaillement d'intensité moyenne à forte.</p> <p>La schistosité est disposée entre 15°-25°ac et parfois selon l'ac.</p>	123.39	125.00	D015478	1.61	0.017		0.017
			125.00	126.50	D015479	1.50	0.086		0.086
			126.50	128.00	D015481	1.50	0.137		0.137
			128.00	129.50	D015483	1.50	0.121		0.121
			129.50	131.00	D015484	1.50	0.012		0.012
			131.00	132.60	D015485	1.60	<0.005		0.001
			132.60	134.20	D015486	1.60	<0.005		0.001
			134.20	135.74	D015487	1.54	0.006		0.006
			135.74	136.87	D015488	1.13	<0.005		0.001
135.74	138.43	<p>SY; FIN</p> <p><b>Syénite 50°; Grains fins</b></p> <p>Syénite altérée beige et rosée, foliée par endroits et affectée par des cisaillements étroits.</p> <p>La texture porphyrique est évidente par endroits. Les porphyres sont souvent chloritisés, verdâtre et hématisés, rosés.</p> <p>La foliation se retrouve entre 30°-40°ac.</p> <p>La syénite est carbonatisée par endroits.</p> <p>Nous observons deux (2) zones de cisaillement à 45°ac, variant de 10-25cm en épaisseur.</p>							
136.20	136.45	<p>CIS</p> <p><b>Cisaillement 40°</b></p> <p>Cisaillement d'intensité moyenne, ayant une épaisseur de 10cm.</p> <p>La syénite est chloritisée et carbonatisée.</p> <p>Recoupée par des veinules de carbonates.</p>							
136.86	137.23	<p>CIS</p> <p><b>Cisaillement 35°</b></p> <p>Cisaillement occupé par une veine de quartz-carbonates-chlorite, gris foncé, ayant environ 15cm en épaisseur. Minéralisée en pyrite (tr-1%) en cubes moyens.</p> <p>Nous observons un système de veinules de feldspaths roses-quartz et tourmaline, disposé à 55°ac et ne dépassant 5cm en épaisseur. Minéralisation de pyrite</p>	136.87	138.43	D015489	1.56	0.015		0.015
138.43	149.45	<p>SY; POR</p> <p><b>Syénite 35°; Porphyrique</b></p> <p>Syénite porphyrique rosée, roâtre et parfois ocre.</p> <p>Elle est massive et assez homogène en composition.</p> <p>Faiblement magnétique.</p> <p>Les porphyres de feldspaths se présentent hypi à idiomorphes. Le</p>	138.43	140.00	D015490	1.57	<0.005		0.001
			140.00	141.50	D015491	1.50	<0.005		0.001
			141.50	143.00	D015493	1.50	<0.005		0.001
			143.00	144.50	D015494	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
149.45	162.87	<p>pourtour est parfois chloritisé.</p> <p>Nous observons plusieurs fractures occupées par des veinules de carbonates et disposées à 55°ac.</p>	144.50	146.00	D015495	1.50	<0.005		0.001			
			146.00	147.15	D015496	1.15	<0.005		0.001			
			147.15	148.30	D015497	1.15	<0.005		0.001			
			148.30	149.45	D015498	1.15	<0.005		0.001			
				SY; MTY	149.45	150.70	D015499	1.25	2.240		2.240	
				<b>Syénite 65°; Grains moyens</b>	150.70	152.00	D015500	1.30	0.319		0.319	
				Syénite rosâtre, rose verdâtre par endroits.	152.00	153.50	D015501	1.50	1.040		1.040	
				Nous observons quelques porphyres de feldspaths dispersés ici et là. Sa composition est assez homogène et faiblement magnétique par endroits.	153.50	155.00	D015503	1.50	0.333		0.333	
149.45	150.11	<p>Elle est affectée par des zones de cisaillement, chloritisées.</p> <p>CIS</p> <p><b>Cisaillement 45°</b></p> <p>Cisaillement d'intensité forte et ayant une épaisseur d'environ 0.45m.</p> <p>La syénite est complètement chloritisé, verdâtre.</p> <p>Nous observons un système de veinules de quartz-carbonates-albite et chlorite-tourmaline, disposées selon la déformation. Elles varient de 1-6cm en épaisseur et représentent environ 50% du volume de la carotte.</p> <p>La tourmaline est amorphe et se présente dans des fractures. Minéralisation de pyrite fine (tr-1%) surtout présente dans les épontes.</p>										
			154.10	154.30	CIS	155.00	156.50	D015504	1.50	0.763		0.763
					<b>Cisaillement 40°</b>	156.50	158.00	D015505	1.50	0.110		0.110
					Cisaillement d'intensité moyenne et ayant une épaisseur de 10cm.	158.00	159.50	D015506	1.50	0.055		0.055
					La syénite est chloritisée et carbonatisée.							
			158.41	159.30	CIS	159.50	161.00	D015507	1.50	0.052		0.052
					<b>Cisaillement 60°</b>	161.00	162.40	D015508	1.40	0.220		0.220
					Cisaillement d'intensité moyenne à forte.	162.40	164.00	D015509	1.60	0.459		0.459
					La syénite est hématisée, carbonatisée et fortement chloritisée par endroits.							
					Les porphyres de feldspaths sont allongés, étirés selon la déformation.							
		Nous observons un système de veinules et veines de quartz-feldspaths roses-carbonates et chlorite-tourmaline, variant de 2-3mm à 12cm en épaisseur.										

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		En volume, ce système représente environ 25% de la carotte.							
162.45	162.71	CIS <b>Cisaillement 60°</b> Cisaillement d'intensité forte, ayant 20cm en épaisseur. Injecté par un système de veinules de quartz-feldspaths roses-carbonates et chlorite-tourmaline amorphe. Stérile en sulfures.							
162.87	278.00	SY; POR; MAS <b>Syénite; Porphyrique; Roche massive</b> Syénite porphyrique massive, porphyrique, rose, rosâtre et parfois ocre. Sa composition est assez homogène. Elle est surtout hématisée. Elle se compose entre 15-20% de feldspaths porphyriques, hypi à idiomorphes, pouvant atteindre jusqu'à 1.5x1.5cm en dimensions. Nous observons plusieurs fractures occupées par des veinules de carbonates-albite et ne dépassant 4-5mm en épaisseur. Elles sont disposées entre 10°-60°ac. Présence de quelques veinules de quartz gris foncé, ne dépassant 2cm en épaisseur. Elles contiennent parfois des traces de chalcoppyrite. Par endroits, la syénite est chloritisée, de teinte vert pâle. Les porphyres sont vert foncé, chloritisés. Dans des zones déformées (schistosées, foliées), la texture porphyrique est peu évidente. Parfois, la syénite est d'aspect bréchiqque. Présence de quelques veinules de quartz-chlorite-carbonates, disposées entre 45°-80°ac et ne dépassant 5cm en épaisseur. Tarces de pyrite finement disséminée.	164.00	165.50	D015510	1.50	0.053		0.053
			165.50	167.00	D015511	1.50	0.017		0.017
			167.00	168.50	D015513	1.50	0.164		0.164
			168.50	170.00	D015514	1.50	0.731		0.731
			170.00	171.50	D015515	1.50	0.524		0.524
			171.50	173.00	D015516	1.50	<0.005		0.001
			173.00	174.50	D015517	1.50	0.020		0.020
			174.50	176.00	D015518	1.50	<0.005		0.001
			176.00	177.50	D015519	1.50	<0.005		0.001
			177.50	179.00	D015521	1.50	0.015		0.015
			179.00	180.50	D015523	1.50	<0.005		0.001
			180.50	182.00	D015524	1.50	<0.005		0.001
			182.00	183.50	D015525	1.50	0.018		0.018
			183.50	185.00	D015526	1.50	<0.005		0.001
			185.00	186.50	D015527	1.50	<0.005		0.001
			186.50	188.00	D015528	1.50	<0.005		0.001
			188.00	189.50	D015529	1.50	<0.005		0.001
			189.50	191.00	D015530	1.50	<0.005		0.001
			191.00	192.50	D015531	1.50	<0.005		0.001
			192.50	194.00	D015533	1.50	<0.005		0.001
			194.00	195.17	D015534	1.17	<0.005		0.001
			195.17	196.34	D015535	1.17	<0.005		0.001
196.34	197.15	CH; SR; CB <b>Chloriteux; Séricitique; Carbonaté</b> La syénite est de teinte vert pâle. Les feldspaths sont en majorité de teinte vert foncé. Ils sont étirés, allongés. C'est une zone de cisaillement, présente à 45°ac.	196.34	197.15	D015536	0.81	<0.005		0.001
			197.15	198.40	D015537	1.25	<0.005		0.001
			198.40	199.50	D015538	1.10	<0.005		0.001
			199.50	200.83	D015539	1.33	0.038		0.038
200.83	203.32	CH; SR; CB <b>Chloriteux; Séricitique; Carbonaté</b>	200.83	202.10	D015540	1.27	0.026		0.026



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		La syénite est de teinte vert pâle.	202.10	203.32	D015541	1.22	<0.005		0.001
		Les porphyres de feldspaths sont chloritisés, vert foncé.	203.32	204.65	D015543	1.33	<0.005		0.001
			204.65	206.00	D015544	1.35	<0.005		0.001
			206.00	207.50	D015545	1.50	<0.005		0.001
			207.50	209.00	D015546	1.50	<0.005		0.001
			209.00	210.50	D015547	1.50	<0.005		0.001
			210.50	212.00	D015548	1.50	<0.005		0.001
			212.00	213.50	D015549	1.50	0.008		0.008
			213.50	215.00	D015550	1.50	<0.005		0.001
			215.00	216.50	D015551	1.50	0.010		0.010
			216.50	218.00	D015553	1.50	0.007		0.007
			218.00	219.50	D015554	1.50	0.165		0.165
			219.50	221.00	D015555	1.50	<0.005		0.001
			221.00	222.50	D015556	1.50	0.018		0.018
			222.50	224.00	D015557	1.50	0.218		0.218
			224.00	225.50	D015558	1.50	0.015		0.015
			225.50	227.00	D015559	1.50	0.014		0.014
			227.00	228.50	D015561	1.50	0.046		0.046
227.48	228.30	CH; CB	228.50	230.00	D015563	1.50	0.366		0.366
		<b>Chloriteux; Carbonaté</b>	230.00	231.50	D015564	1.50	0.785		0.785
		La syénite est vert pâle.	231.50	233.00	D015565	1.50	0.152		0.152
		Les porphyres de feldspaths sont vert foncé, chloritisés.	233.00	234.50	D015566	1.50	0.005		0.005
			234.50	236.00	D015567	1.50	<0.005		0.001
			236.00	237.50	D015568	1.50	0.025		0.025
			237.50	239.00	D015569	1.50	0.474		0.474
			239.00	240.50	D015570	1.50	0.390		0.390
			240.50	242.00	D015571	1.50	0.795		0.795
			242.00	243.50	D015573	1.50	0.048		0.048
			243.50	245.00	D015574	1.50	0.314		0.314
			245.00	246.50	D015575	1.50	0.105		0.105
246.02	247.82	CH; CB; SR							
		<b>Chloriteux; Carbonaté; Séricitique</b>							
		La syénite est de teinte vert pâle, vert lime.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
246.02	247.82	CIS <b>Cisaillement 30°</b> Cisaillement d'intensité faible à moyenne, avec de zones bréchiques.	246.50	248.00	D015576	1.50	<0.005		0.001
			248.00	249.50	D015577	1.50	<0.005		0.001
			249.50	251.00	D015578	1.50	<0.005		0.001
			251.00	252.50	D015579	1.50	<0.005		0.001
			252.50	254.00	D015580	1.50	<0.005		0.001
253.60	253.90	CIS <b>Cisaillement 50°</b> Cisaillement d'intensité moyenne. Son épaisseur est d'environ 18cm. Présence de veinules de quartz-carbonates-chlorite, stériles en sulfures.	254.00	255.50	D015581	1.50	0.044		0.044
			255.50	257.00	D015583	1.50	0.012		0.012
			257.00	258.50	D015584	1.50	0.146		0.146
			258.50	260.00	D015585	1.50	<0.005		0.001
			260.00	261.50	D015586	1.50	<0.005		0.001
			261.50	263.00	D015587	1.50	<0.005		0.001
			263.00	264.50	D015588	1.50	0.012		0.012
			264.50	266.00	D015589	1.50	0.023		0.023
			266.00	267.50	D015590	1.50	0.091		0.091
			267.50	269.00	D015591	1.50	0.045		0.045
			269.00	270.50	D015593	1.50	0.164		0.164
			270.50	272.00	D015594	1.50	0.144		0.144
			272.00	273.50	D015595	1.50	0.174		0.174
			273.50	275.00	D015596	1.50	0.362		0.362
275.00	276.50	D015597	1.50	0.522		0.522			
276.50	278.00	D015598	1.50	0.402		0.402			
278.00	289.80	TU; LAM <b>Tuf à cendre/lapillis; Laminations parallèles</b> Séquence de pyroclastites de composition felsique, grisâtre, beige. Ils sont représentés par des tufs fins et à lapillis, à cristaux de quartz et de feldspaths. Ils se présentent généralement arrondis. Le litage est évident parfois et est disposé à 50°ac. Ils sont séricitisés, carbonatisés et silicifiés par endroits. Minéralisation de pyrite fine (2-4%), disséminée et concentrée selon la déformation. La schistosité est bien développée, accompagnée de plissement par endroits.	278.00	279.50	D015599	1.50	0.485		0.485
			279.50	281.00	D015601	1.50	0.916		0.916
			281.00	282.50	D015603	1.50	1.705		1.705
			282.50	284.00	D015604	1.50	3.470		3.470
			284.00	285.50	D015605	1.50	5.700		5.700
			285.50	287.00	D015606	1.50	1.995		1.995
			287.00	288.40	D015607	1.40	2.330		2.330
			288.40	289.80	D015608	1.40	0.571		0.571
289.80	293.60	RY; SPH <b>Rhyolite; Sphérolitique</b> Rhyolite gris foncé, grisâtre et beige. Elle se présente à grains fins, dure et nous observons plusieurs	289.80	291.30	D015609	1.50	1.865		1.865
			291.30	292.40	D015610	1.10	2.340		2.340
			292.40	293.60	D015611	1.20	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<p>sphérolites (?) occupées surtout par du quartz et parfois de chlorite.                      Cette coulée est d'aspect bréchique, dont les fractures sont occupées essentiellement par de la chlorite. Elles s'entrecroisent formant un bon réseau par endroits.                      Minéralisation de pyrite fine (2-3%) concentrée selon des lentilles discontinues et disséminée.</p>							
293.60	296.67	TU; LAM	293.60	295.10	D015613	1.50	0.008		0.008
		<b>Tuf à cendre/lapillis 30°; Laminations parallèles</b>	295.10	296.67	D015614	1.57	0.005		0.005
		<p>Séquence de tufs à cendres et lapillis, de composition felsique, gris foncé, grisâtre et beige.                      Ils se composent de cristaux de quartz et de feldspaths.                      Ils sont durs, silicifiés et séricitisés.&lt;br&gt;Le litage est disposé à 35°ac.</p>							
296.67	338.70	BA; COU; AMY	296.67	297.85	D015615	1.18	0.013		0.013
		<b>Basalte 35°; Coussiné; Amygdalaire</b>	297.85	299.00	D015616	1.15	0.005		0.005
		<p>Basalte coussiné, amygdalaire, vert foncé, vert pâle, grisâtre et beige.                      La structure de coussins est évidente.                      Présence d'amygdules, occupées par des carbonates, quartz et chlorite parfois.                      Peut contenir de minces bandes de tufs à cendres.                      Un schistosité est présente à 35°ac.</p>	299.00	300.50	D015617	1.50	0.006		0.006
			300.50	302.00	D015618	1.50	0.009		0.009
			302.00	303.50	D015619	1.50	0.007		0.007
			303.50	305.00	D015620	1.50	0.005		0.005
			305.00	306.50	D015621	1.50	<0.005		0.001
			306.50	308.00	D015623	1.50	0.005		0.005
			308.00	309.50	D015624	1.50	<0.005		0.001
			309.50	311.00	D015625	1.50	<0.005		0.001
			311.00	312.50	D015626	1.50	<0.005		0.001
			312.50	314.00	D015627	1.50	<0.005		0.001
			314.00	315.50	D015628	1.50	<0.005		0.001
			315.50	317.00	D015629	1.50	<0.005		0.001
			317.00	318.50	D015630	1.50	<0.005		0.001
			318.50	320.00	D015631	1.50	<0.005		0.001
			320.00	321.50	D015633	1.50	<0.005		0.001
			321.50	323.00	D015634	1.50	<0.005		0.001
			323.00	324.50	D015635	1.50	<0.005		0.001
			324.50	326.00	D015636	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
338.70	341.00	TU <b>Tuf à cendre/lapillis 35°</b> Séquence de tufs à lapillis, blocs et bombes. Sa composition est basique. Les fragments révèlent une composition de basalte amygdalaire.	326.00	327.50	D015637	1.50	<0.005		0.001
			327.50	329.00	D015638	1.50	0.005		0.005
			329.00	330.50	D015639	1.50	<0.005		0.001
			330.50	332.00	D015641	1.50	<0.005		0.001
			332.00	333.50	D015643	1.50	<0.005		0.001
			333.50	335.00	D015644	1.50	<0.005		0.001
			335.00	336.20	D015645	1.20	<0.005		0.001
			336.20	337.40	D015646	1.20	<0.005		0.001
			337.40	338.70	D015647	1.30	<0.005		0.001
			338.70	339.85	D015648	1.15	<0.005		0.001
			339.85	341.00	D015649	1.15	<0.005		0.001
			341.00	Fin du sondage Nombre d'échantillons : 229 Nombre d'échantillons QAQC : 33 Longueur totale échantillonnée : 335.00					

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.50	11.00	D015392	D015391	1.50	<0.005	0.001
20.00	21.50	D015400	M1	1.50	<0.005	0.001
21.50	23.00	D015402	J	1.50	0.732	0.732
35.00	36.50	D015412	D015411	1.50	0.005	0.005
48.50	50.00	D015422	K	1.50	1.025	1.025
62.00	63.50	D015432	D015431	1.50	<0.005	0.001
72.50	74.00	D015440	M1	1.50	<0.005	0.001
74.00	75.50	D015442	L	1.50	2.270	2.270
87.50	89.00	D015452	D015451	1.50	0.157	0.157
101.00	102.50	D015462	M	1.50	3.250	3.250
114.50	116.00	D015472	D015471	1.50	<0.005	0.001
125.00	126.50	D015480	M1	1.50	<0.005	0.001
126.50	128.00	D015482	J	1.50	0.741	0.741
140.00	141.50	D015492	D015491	1.50	<0.005	0.001
152.00	153.50	D015502	K	1.50	0.960	0.960
165.50	167.00	D015512	D015511	1.50	0.034	0.034
176.00	177.50	D015520	M1	1.50	<0.005	0.001
177.50	179.00	D015522	L	1.50	2.070	2.070
191.00	192.50	D015532	D015531	1.50	<0.005	0.001
202.10	203.32	D015542	M	1.22	3.040	3.040
215.00	216.50	D015552	D015551	1.50	0.008	0.008
225.50	227.00	D015560	M1	1.50	<0.005	0.001
227.00	228.50	D015562	J	1.50	0.791	0.791
240.50	242.00	D015572	D015571	1.50	0.845	0.845
254.00	255.50	D015582	K	1.50	1.080	1.080
267.50	269.00	D015592	D015591	1.50	0.057	0.057
278.00	279.50	D015600	M1	1.50	<0.005	0.001
279.50	281.00	D015602	L	1.50	2.250	2.250
292.40	293.60	D015612	D015611	1.20	0.015	0.015
305.00	306.50	D015622	M	1.50	3.120	3.120
318.50	320.00	D015632	D015631	1.50	<0.005	0.001
329.00	330.50	D015640	M1	1.50	<0.005	0.001
330.50	332.00	D015642	J	1.50	0.785	0.785

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-190**

Titre minier :

Section :                      630400

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Johan Bergé

Lot :

Du :                      2010-04-25

Date de description :

Au :                      2010-04-27

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      199.00 m

Est	630 399.7
Nord	5 374 500.5
Élévation	297.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	359.10°	-59.70°	Non
Reflex	8.00	359.20°	-59.80°	Non
Reflex	11.00	359.10°	-59.80°	Non
Reflex	14.00	359.60°	-59.90°	Non
Reflex	17.00	359.90°	-59.80°	Non
Reflex	20.00	0.30°	-60.00°	Non
Reflex	23.00	0.50°	-60.00°	Non
Reflex	26.00	359.80°	-60.10°	Non
Reflex	29.00	359.30°	-60.10°	Non
Reflex	32.00	1.60°	-60.10°	Non
Reflex	35.00	4.40°	-60.10°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.80°	-60.20°	Non
Reflex	41.00	3.10°	-60.20°	Non
Reflex	44.00	357.80°	-60.30°	Oui
Reflex	47.00	359.20°	-60.30°	Oui
Reflex	50.00	3.60°	-60.30°	Non
Reflex	53.00	1.40°	-60.40°	Non
Reflex	56.00	1.40°	-60.30°	Non
Reflex	59.00	3.70°	-60.30°	Oui
Reflex	62.00	0.40°	-60.30°	Non
Reflex	65.00	0.50°	-60.30°	Non
Reflex	68.00	1.70°	-60.40°	Non
Reflex	71.00	1.70°	-60.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.60°	-60.30°	Non	Reflex	173.00	6.20°	-61.20°	Non
Reflex	77.00	1.20°	-60.30°	Non	Reflex	176.00	6.20°	-61.10°	Non
Reflex	80.00	1.20°	-60.30°	Non	Reflex	179.00	6.20°	-61.20°	Non
Reflex	83.00	1.80°	-60.20°	Non	Reflex	182.00	6.10°	-61.20°	Non
Reflex	86.00	1.20°	-60.20°	Non	Reflex	185.00	6.40°	-61.30°	Non
Reflex	89.00	1.60°	-60.20°	Non	Reflex	188.00	6.40°	-61.20°	Non
Reflex	92.00	3.20°	-60.30°	Oui	Reflex	191.00	5.90°	-61.20°	Non
Reflex	95.00	359.40°	-60.30°	Non	Reflex	194.00	5.90°	-61.20°	Non
Reflex	98.00	4.70°	-60.40°	Oui	Reflex	197.00	6.00°	-61.30°	Non
Reflex	101.00	1.90°	-60.40°	Non					
Reflex	104.00	4.20°	-60.40°	Non					
Reflex	107.00	4.60°	-60.40°	Non					
Reflex	110.00	3.90°	-60.40°	Non					
Reflex	113.00	4.40°	-60.50°	Non					
Reflex	116.00	3.40°	-60.60°	Non					
Reflex	119.00	4.70°	-60.60°	Non					
Reflex	122.00	1.90°	-60.60°	Oui					
Reflex	125.00	3.60°	-60.60°	Non					
Reflex	128.00	0.30°	-60.70°	Oui					
Reflex	131.00	2.20°	-60.70°	Non					
Reflex	134.00	5.60°	-60.80°	Oui					
Reflex	137.00	3.40°	-60.90°	Non					
Reflex	140.00	5.40°	-60.90°	Oui					
Reflex	143.00	4.70°	-61.00°	Non					
Reflex	146.00	6.20°	-61.00°	Non					
Reflex	149.00	4.90°	-61.00°	Oui					
Reflex	152.00	7.50°	-61.00°	Oui					
Reflex	155.00	6.40°	-61.10°	Non					
Reflex	158.00	5.40°	-61.10°	Non					
Reflex	161.00	5.40°	-61.10°	Non					
Reflex	164.00	6.50°	-61.20°	Non					
Reflex	167.00	5.70°	-61.20°	Non					
Reflex	170.00	6.00°	-61.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	5.80	MT <b>Mort-terrain</b> No recovery.							
5.80	61.00	SY <b>Syénite</b> Syénite massive avec phénocristaux, à passage porphyrique à grain de taille mm à cm. Les feldspaths blancs sont les minéraux les plus gros. La quasitotalité de l'unité est carbonatée. Lithologie très magnétique. La couleur est lié à l'altération. Vert chlorite, rouge hématite, rouille ankérite, brun séricite. La pyrite est disséminée et très fine.	5.80	7.00	D031001	1.20	<0.005		0.001
			7.00	8.00	D031002	1.00	<0.005		0.001
			8.00	9.50	D031004	1.50	<0.005		0.001
			9.50	11.00	D031005	1.50	<0.005		0.001
			11.00	12.50	D031006	1.50	<0.005		0.001
			12.50	14.00	D031007	1.50	<0.005		0.001
			14.00	15.50	D031008	1.50	<0.005		0.001
			15.50	17.00	D031009	1.50	<0.005		0.001
			17.00	18.50	D031011	1.50	<0.005		0.001
			18.50	20.00	D031012	1.50	0.013		0.013
			20.00	21.50	D031014	1.50	<0.005		0.001
			21.50	23.00	D031015	1.50	<0.005		0.001
			23.00	24.50	D031016	1.50	<0.005		0.001
			24.50	26.00	D031017	1.50	0.007		0.007
26.00	36.50	SR <b>Séricitique</b> Réseau de cheveux/veinules de séricite et petits grain millimétriques.	26.00	27.50	D031018	1.50	0.025		0.025
			27.50	29.00	D031019	1.50	0.066		0.066
			29.00	30.50	D031020	1.50	0.007		0.007
			30.50	32.00	D031021	1.50	0.038		0.038
			32.00	33.50	D031022	1.50	0.007		0.007
			33.50	35.00	D031024	1.50	<0.005		0.001
			35.00	36.50	D031025	1.50	0.015		0.015
			36.50	38.00	D031026	1.50	0.006		0.006
			38.00	39.50	D031027	1.50	<0.005		0.001
			39.50	41.00	D031028	1.50	<0.005		0.001
			41.00	42.50	D031029	1.50	0.009		0.009
			42.50	44.00	D031030	1.50	<0.005		0.001
			44.00	45.50	D031031	1.50	0.015		0.015
			45.50	47.00	D031032	1.50	<0.005		0.001
			47.00	48.50	D031034	1.50	0.008		0.008
			48.50	50.00	D031035	1.50	0.021		0.021
			50.00	51.50	D031036	1.50	0.031		0.031



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
61.00	81.00	<b>SY</b> <b>Syénite</b> Syénite massive avec très peu de phénocristaux. Les feldspaths blancs sont les minéraux les plus gros. La quasitotalité de l'unité est carbonatée. Lithologie très magnétique. La couleur est lié à l'altération. Vert chlorite, rouge hématite, rouille ankérite, brun séricite. La pyrite est disséminée et très fine.	51.50	53.00	D031037	1.50	0.026		0.026
			53.00	54.50	D031038	1.50	0.020		0.020
			54.50	56.00	D031039	1.50	0.041		0.041
			56.00	57.50	D031040	1.50	<0.005		0.001
			57.50	59.00	D031041	1.50	<0.005		0.001
			59.00	60.50	D031042	1.50	0.028		0.028
			60.50	62.00	D031044	1.50	<0.005		0.001
			62.00	63.50	D031045	1.50	0.008		0.008
			63.50	65.00	D031046	1.50	0.008		0.008
63.90	73.00	<b>CH</b> <b>Chloriteux</b> Avec des passages épidotisés.	65.00	66.50	D031047	1.50	0.041		0.041
			66.50	68.00	D031048	1.50	0.016		0.016
			68.00	69.50	D031049	1.50	0.018		0.018
			69.50	71.00	D031051	1.50	0.028		0.028
			71.00	72.50	D031052	1.50	0.015		0.015
			72.50	74.00	D031054	1.50	0.044		0.044
73.00	81.00	<b>SR</b> <b>Séricitique</b>	74.00	75.50	D031055	1.50	0.440		0.440
			75.50	77.00	D031056	1.50	0.307		0.307
			77.00	78.50	D031057	1.50	0.134		0.134
			78.50	80.00	D031058	1.50	0.238		0.238
			80.00	81.50	D031059	1.50	0.167		0.167
81.00	140.00	<b>SY</b> <b>Syénite</b> Syénite avec 30% de phénocristaux. Les feldspaths blancs sont les minéraux les plus gros. La quasitotalité de l'unité est carbonatée. Lithologie très magnétique. La couleur est lié à l'altération. Vert chlorite, rouge hématite, rouille	81.50	83.00	D031060	1.50	0.008		0.008
			83.00	84.50	D031061	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
ankérite, brun séricite. La pyrite est disséminée et très fine.								
81.00	84.00	HM <b>Hématisé</b>						
84.00	89.00	CH <b>Chloriteux</b>	84.50	86.00	D031062	1.50	0.063	0.063
			86.00	87.50	D031064	1.50	0.055	0.055
			87.50	89.00	D031065	1.50	0.010	0.010
89.00	151.00	HM <b>Hématisé</b> Avec passage chloriteux.	89.00	90.50	D031066	1.50	0.008	0.008
			90.50	92.00	D031067	1.50	<0.005	0.001
			92.00	93.50	D031068	1.50	<0.005	0.001
			93.50	95.00	D031069	1.50	<0.005	0.001
			95.00	96.50	D031070	1.50	<0.005	0.001
			96.50	98.00	D031071	1.50	0.005	0.005
			98.00	99.50	D031072	1.50	<0.005	0.001
			99.50	101.00	D031074	1.50	0.005	0.005
			101.00	102.50	D031075	1.50	<0.005	0.001
			102.50	104.00	D031076	1.50	<0.005	0.001
			104.00	105.50	D031077	1.50	0.014	0.014
			105.50	107.00	D031078	1.50	0.007	0.007
			107.00	108.50	D031079	1.50	0.015	0.015
			108.50	110.00	D031080	1.50	<0.005	0.001
			110.00	111.50	D031081	1.50	0.009	0.009
			111.50	113.00	D031082	1.50	<0.005	0.001
			113.00	114.50	D031084	1.50	0.013	0.013
			114.50	116.00	D031085	1.50	0.014	0.014
			116.00	117.50	D031086	1.50	0.005	0.005
			117.50	119.00	D031087	1.50	<0.005	0.001
			119.00	120.50	D031088	1.50	<0.005	0.001
			120.50	122.00	D031089	1.50	<0.005	0.001
			122.00	123.50	D031091	1.50	0.025	0.025
			123.50	125.00	D031092	1.50	<0.005	0.001
			125.00	126.50	D031094	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
140.00	198.50	SY <b>Syénite</b> Syénite massive avec peu de phénocristaux. Les feldspaths blancs sont les minéraux les plus gros. La quasitotalité de l'unité est carbonatée. Lithologie peu magnétique avec passages très magnétiques décimétriques. La couleur est lié à l'altération. Vert chlorite, rouge hématite, rouille ankérite, brun séricite. La pyrite est disséminée et très fine.	126.50	128.00	D031095	1.50	0.010		0.010
			128.00	129.50	D031096	1.50	0.021		0.021
			129.50	131.00	D031097	1.50	<0.005		0.001
			131.00	132.50	D031098	1.50	0.006		0.006
			132.50	134.00	D031099	1.50	<0.005		0.001
			134.00	135.50	D031100	1.50	<0.005		0.001
			135.50	137.00	D031101	1.50	<0.005		0.001
			137.00	138.50	D031102	1.50	<0.005		0.001
			138.50	140.00	D031104	1.50	<0.005		0.001
			140.00	141.50	D031105	1.50	0.006		0.006
			141.50	143.00	D031106	1.50	0.007		0.007
			143.00	144.00	D031107	1.00	0.019		0.019
144.00	145.50	D031108	1.50	0.017		0.017			
145.50	147.00	D031109	1.50	<0.005		0.001			
147.00	148.50	D031110	1.50	<0.005		0.001			
148.50	150.00	D031111	1.50	0.005		0.005			
150.00	151.50	D031112	1.50	<0.005		0.001			
151.00	157.00	CH <b>Chloriteux</b> Avec des passages séricitisés.	151.50	153.00	D031114	1.50	<0.005		0.001
			153.00	154.50	D031115	1.50	<0.005		0.001
			154.50	156.00	D031116	1.50	<0.005		0.001
			156.00	157.50	D031117	1.50	0.010		0.010
157.00	171.50	HM <b>Hématisé</b>	157.50	159.00	D031118	1.50	0.010		0.010
			159.00	160.50	D031119	1.50	<0.005		0.001
			160.50	162.00	D031120	1.50	<0.005		0.001
			162.00	163.50	D031121	1.50	0.005		0.005
			163.50	165.00	D031122	1.50	0.008		0.008
			165.00	166.50	D031124	1.50	0.008		0.008
			166.50	168.00	D031125	1.50	0.008		0.008
			168.00	169.50	D031126	1.50	<0.005		0.001
			169.50	171.00	D031127	1.50	0.012		0.012
			171.00	172.50	D031128	1.50	0.146		0.146

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
171.50	179.00	CH Chloriteux	172.50	174.00	D031129	1.50	0.022		0.022
			174.00	175.50	D031131	1.50	0.018		0.018
			175.50	177.00	D031132	1.50	0.117		0.117
			177.00	178.50	D031134	1.50	0.084		0.084
			178.50	180.00	D031135	1.50	0.028		0.028
179.00	185.00	HM Hématisé	180.00	181.50	D031136	1.50	0.032		0.032
			181.50	183.00	D031137	1.50	0.037		0.037
			183.00	184.50	D031138	1.50	0.063		0.063
			184.50	186.00	D031139	1.50	0.036		0.036
185.00	198.50	CH Chloriteux Avec passage séricitisés.	186.00	187.50	D031140	1.50	0.018		0.018
			187.50	189.20	D031141	1.70	0.017		0.017
			189.20	190.60	D031142	1.40	0.103		0.103
			190.60	192.00	D031144	1.40	0.008		0.008
			192.00	193.10	D031145	1.10	0.009		0.009
			193.10	194.50	D031146	1.40	0.016		0.016
			194.50	196.00	D031147	1.50	0.012		0.012
			196.00	197.00	D031148	1.00	0.133		0.133
		197.00	198.50	D031149	1.50	0.012		0.012	
198.50	199.00	NR Carotte perdue Il manque 0.50m d'après le dernier bloc (EOH=199m).							
199.00	Fin du sondage Nombre d'échantillons : 130 Nombre d'échantillons QAQC : 19 Longueur totale échantillonnée : 192.70								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
7.00	8.00	D031003	D031002	1.00	<0.005	0.001
15.50	15.50	D031010	M1	0.00	<0.005	0.001
18.50	18.50	D031013	J	0.00	0.734	0.734
32.00	33.50	D031023	D031022	1.50	0.005	0.005
45.50	45.50	D031033	K	0.00	1.125	1.125
59.00	60.50	D031043	D031042	1.50	0.018	0.018
68.00	68.00	D031050	M1	0.00	<0.005	0.001
71.00	71.00	D031053	L	0.00	2.250	2.250
84.50	86.00	D031063	D031062	1.50	0.063	0.063
98.00	98.00	D031073	M	0.00	3.030	3.030
111.50	113.00	D031083	D031082	1.50	<0.005	0.001
120.50	120.50	D031090	M1	0.00	<0.005	0.001
123.50	123.50	D031093	J	0.00	0.769	0.769
137.00	138.50	D031103	D031102	1.50	<0.005	0.001
150.00	150.00	D031113	K	0.00	1.070	1.070
163.50	165.00	D031123	D031122	1.50	0.014	0.014
172.50	172.50	D031130	M1	0.00	<0.005	0.001
175.50	175.50	D031133	L	0.00	2.080	2.080
189.20	190.60	D031143	D031142	1.40	0.100	0.100

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-191</b>	Titre minier :	Section :	629 900
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-04-28	Date de description :	
	Au : 2010-04-29		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 47.70 m

UTM

Est	629 899.9
Nord	5 374 201.7
Élévation	279.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	0.00°	-60.00°	Non
Reflex	10.00	0.00°	-60.00°	Non
Reflex	20.00	0.00°	-60.00°	Non
Reflex	30.00	0.00°	-60.00°	Non
Reflex	40.00	0.00°	-60.00°	Non
Reflex	47.70	0.00°	-60.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	39.00	MT						
		<b>Mort-terrain</b>						
39.00	47.70	BA; MAS; AMY	39.00	40.50	D002454	1.50	<0.005	0.001
		<b>Basalte; Roche massive; Amygdalaire</b>	40.50	42.00	D002455	1.50	<0.005	0.001
		microlitique, localement altéré en calcite et chlorite, légèrement séricitisé, PY irrég diss	42.00	43.50	D002456	1.50	0.006	0.006
			43.50	45.00	D002457	1.50	0.028	0.028
			45.00	46.50	D002459	1.50	0.005	0.005
			46.50	47.70	D002460	1.20	<0.005	0.001
47.70		Fin du sondage						
		Nombre d'échantillons : 6						
		Nombre d'échantillons QAQC : 1						
		Longueur totale échantillonnée : 8.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
43.50	45.00	D002458	D002457	1.50	0.025	0.025



## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-191B</b>	Titre minier :	Section :	629900
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Guy Gbaguidi & Gilles Kamta	Du : 2010-05-04	Date de description :	2010-06-11
	Au : 2010-05-08		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 350.00 m

UTM

Est	629 899.9
Nord	5 374 201.7
Élévation	279.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	358.30°	-61.00°	Oui
Reflex	8.00	358.00°	-60.60°	Oui
Reflex	11.00	339.20°	-60.40°	Oui
Reflex	14.00	4.30°	-60.30°	Oui
Reflex	17.00	5.30°	-60.30°	Oui
Reflex	20.00	345.70°	-60.40°	Oui
Reflex	23.00	336.60°	-60.50°	Oui
Reflex	26.00	6.80°	-60.80°	Oui
Reflex	29.00	4.50°	-61.50°	Oui
Reflex	32.00	3.50°	-61.80°	Oui
Reflex	35.00	338.10°	-61.40°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	328.10°	-61.40°	Oui
Reflex	41.00	4.40°	-61.50°	Oui
Reflex	44.00	350.00°	-61.60°	Oui
Reflex	47.00	356.10°	-61.60°	Non
Reflex	50.00	356.10°	-61.70°	Non
Reflex	53.00	355.80°	-61.70°	Non
Reflex	56.00	355.70°	-61.70°	Non
Reflex	59.00	355.40°	-61.70°	Non
Reflex	62.00	355.10°	-61.70°	Non
Reflex	65.00	355.00°	-61.70°	Non
Reflex	68.00	355.00°	-61.50°	Non
Reflex	71.00	355.00°	-61.50°	Non

Description

De 322.5 à 350, décrit par Gilles Kamta

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	38.80	MT						
		<b>Mort-terrain</b>						
0.00	38.80	MT						
		<b>Mort-terrain</b>						
38.80	128.30	GA	38.80	40.00	D022483	1.20	<0.005	0.001
		<b>Gabbro</b>	40.00	41.50	D022484	1.50	0.007	0.007
		Gabbro massive à leucocène carbonaté	41.50	43.00	D022486	1.50	0.008	0.008
			43.00	44.50	D022487	1.50	0.035	0.035
			44.50	46.00	D022488	1.50	0.265	0.265
			46.00	47.50	D022489	1.50	0.049	0.049
			47.50	49.00	D022490	1.50	<0.005	0.001
			49.00	50.50	D022491	1.50	<0.005	0.001
			50.50	52.00	D022492	1.50	<0.005	0.001
			52.00	53.50	D022493	1.50	<0.005	0.001
			53.50	55.00	D022494	1.50	<0.005	0.001
			55.00	56.50	D022496	1.50	<0.005	0.001
			56.50	58.00	D022497	1.50	<0.005	0.001
			58.00	59.50	D022498	1.50	<0.005	0.001
			59.50	61.00	D022499	1.50	<0.005	0.001
			61.00	62.50	D022500	1.50	<0.005	0.001
			62.50	64.00	D022501	1.50	<0.005	0.001
			64.00	65.50	D022502	1.50	<0.005	0.001
			65.50	67.00	D022503	1.50	<0.005	0.001
			67.00	68.50	D022504	1.50	<0.005	0.001
			68.50	70.00	D022506	1.50	<0.005	0.001
			70.00	71.50	D022507	1.50	<0.005	0.001
			71.50	73.00	D022508	1.50	<0.005	0.001
			73.00	74.50	D022509	1.50	<0.005	0.001
			74.50	76.00	D022510	1.50	<0.005	0.001
			76.00	77.50	D022511	1.50	<0.005	0.001
			77.50	79.00	D022512	1.50	0.011	0.011
			79.00	80.50	D022513	1.50	<0.005	0.001
			80.50	82.00	D022514	1.50	<0.005	0.001
			82.00	83.50	D022516	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	83.50	85.00	D022517	1.50	<0.005		0.001
	85.00	86.50	D022518	1.50	<0.005		0.001
	86.50	88.00	D022519	1.50	0.005		0.005
	88.00	89.50	D022521	1.50	0.009		0.009
	89.50	91.00	D022522	1.50	<0.005		0.001
	91.00	92.50	D022523	1.50	<0.005		0.001
	92.50	94.00	D022524	1.50	<0.005		0.001
	94.00	95.50	D022526	1.50	<0.005		0.001
	95.50	97.00	D022527	1.50	<0.005		0.001
	97.00	98.50	D022528	1.50	<0.005		0.001
	98.50	100.00	D022529	1.50	<0.005		0.001
	100.00	101.50	D022530	1.50	0.009		0.009
	101.50	103.00	D022531	1.50	0.005		0.005
	103.00	104.50	D022532	1.50	<0.005		0.001
	104.50	106.00	D022533	1.50	<0.005		0.001
	106.00	107.50	D022534	1.50	<0.005		0.001
	107.50	109.00	D022536	1.50	0.005		0.005
	109.00	110.50	D022537	1.50	<0.005		0.001
	110.50	112.00	D022538	1.50	0.018		0.018
	112.00	113.50	D022539	1.50	0.006		0.006
	113.50	115.00	D022540	1.50	0.015		0.015
	115.00	116.50	D022541	1.50	0.008		0.008
	116.50	118.00	D022542	1.50	<0.005		0.001
	118.00	119.50	D022543	1.50	<0.005		0.001
	119.50	121.00	D022544	1.50	<0.005		0.001
	121.00	122.50	D022546	1.50	<0.005		0.001
	122.50	124.00	D022547	1.50	<0.005		0.001
	124.00	125.50	D022548	1.50	0.005		0.005
	125.50	127.00	D022549	1.50	<0.005		0.001
	127.00	128.30	D022550	1.30	0.015		0.015
38.80	128.30	GA					
		<b>Gabbro</b>					
		Gabbro massive à leucocène carbonaté					
	38.80	40.00	D022483	1.20	<0.005		0.001
	40.00	41.50	D022484	1.50	0.007		0.007
	41.50	43.00	D022486	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	43.00	44.50	D022487	1.50	0.035		0.035
	44.50	46.00	D022488	1.50	0.265		0.265
	46.00	47.50	D022489	1.50	0.049		0.049
	47.50	49.00	D022490	1.50	<0.005		0.001
	49.00	50.50	D022491	1.50	<0.005		0.001
	50.50	52.00	D022492	1.50	<0.005		0.001
	52.00	53.50	D022493	1.50	<0.005		0.001
	53.50	55.00	D022494	1.50	<0.005		0.001
	55.00	56.50	D022496	1.50	<0.005		0.001
	56.50	58.00	D022497	1.50	<0.005		0.001
	58.00	59.50	D022498	1.50	<0.005		0.001
	59.50	61.00	D022499	1.50	<0.005		0.001
	61.00	62.50	D022500	1.50	<0.005		0.001
	62.50	64.00	D022501	1.50	<0.005		0.001
	64.00	65.50	D022502	1.50	<0.005		0.001
	65.50	67.00	D022503	1.50	<0.005		0.001
	67.00	68.50	D022504	1.50	<0.005		0.001
	68.50	70.00	D022506	1.50	<0.005		0.001
	70.00	71.50	D022507	1.50	<0.005		0.001
	71.50	73.00	D022508	1.50	<0.005		0.001
	73.00	74.50	D022509	1.50	<0.005		0.001
	74.50	76.00	D022510	1.50	<0.005		0.001
	76.00	77.50	D022511	1.50	<0.005		0.001
	77.50	79.00	D022512	1.50	0.011		0.011
	79.00	80.50	D022513	1.50	<0.005		0.001
	80.50	82.00	D022514	1.50	<0.005		0.001
	82.00	83.50	D022516	1.50	<0.005		0.001
	83.50	85.00	D022517	1.50	<0.005		0.001
	85.00	86.50	D022518	1.50	<0.005		0.001
	86.50	88.00	D022519	1.50	0.005		0.005
	88.00	89.50	D022521	1.50	0.009		0.009
	89.50	91.00	D022522	1.50	<0.005		0.001
	91.00	92.50	D022523	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			92.50	94.00	D022524	1.50	<0.005		0.001
			94.00	95.50	D022526	1.50	<0.005		0.001
			95.50	97.00	D022527	1.50	<0.005		0.001
			97.00	98.50	D022528	1.50	<0.005		0.001
			98.50	100.00	D022529	1.50	<0.005		0.001
			100.00	101.50	D022530	1.50	0.009		0.009
			101.50	103.00	D022531	1.50	0.005		0.005
			103.00	104.50	D022532	1.50	<0.005		0.001
			104.50	106.00	D022533	1.50	<0.005		0.001
			106.00	107.50	D022534	1.50	<0.005		0.001
			107.50	109.00	D022536	1.50	0.005		0.005
			109.00	110.50	D022537	1.50	<0.005		0.001
			110.50	112.00	D022538	1.50	0.018		0.018
			112.00	113.50	D022539	1.50	0.006		0.006
			113.50	115.00	D022540	1.50	0.015		0.015
			115.00	116.50	D022541	1.50	0.008		0.008
			116.50	118.00	D022542	1.50	<0.005		0.001
			118.00	119.50	D022543	1.50	<0.005		0.001
			119.50	121.00	D022544	1.50	<0.005		0.001
			121.00	122.50	D022546	1.50	<0.005		0.001
			122.50	124.00	D022547	1.50	<0.005		0.001
			124.00	125.50	D022548	1.50	0.005		0.005
			125.50	127.00	D022549	1.50	<0.005		0.001
			127.00	128.30	D022550	1.30	0.015		0.015
128.30	209.00	BA; AMY; MAS	128.30	130.00	D022551	1.70	0.008		0.008
		<b>Basalte; Amygdalaire; Roche massive</b>	130.00	131.50	D022552	1.50	<0.005		0.001
		Basalte carbonaté, localement amygdalaire avec passage d'horizons tuffacés et graphiteux.	131.50	133.00	D022553	1.50	0.006		0.006
			133.00	134.50	D022554	1.50	0.008		0.008
			134.50	136.00	D022556	1.50	0.005		0.005
			136.00	137.50	D022557	1.50	0.006		0.006
			137.50	139.00	D022558	1.50	0.005		0.005
			139.00	140.50	D022559	1.50	<0.005		0.001
			140.50	142.20	D022561	1.70	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	142.20	143.70	D022562	1.50	0.006		0.006
	143.70	145.00	D022563	1.30	0.005		0.005
	145.00	146.50	D022564	1.50	<0.005		0.001
	146.50	148.00	D022566	1.50	0.008		0.008
	148.00	149.00	D022567	1.00	<0.005		0.001
	149.00	150.00	D022568	1.00	<0.005		0.001
	150.00	151.40	D022569	1.40	0.005		0.005
	151.40	153.00	D022570	1.60	0.005		0.005
	153.00	154.00	D022571	1.00	0.006		0.006
	154.00	155.50	D022572	1.50	<0.005		0.001
	155.50	157.00	D022573	1.50	0.005		0.005
	157.00	158.50	D022574	1.50	0.005		0.005
	158.50	160.00	D022576	1.50	0.005		0.005
	160.00	161.50	D022577	1.50	0.005		0.005
	161.50	163.00	D022578	1.50	0.006		0.006
	163.00	164.50	D022579	1.50	<0.005		0.001
	164.50	166.00	D022580	1.50	<0.005		0.001
	166.00	167.50	D022581	1.50	<0.005		0.001
	167.50	169.00	D022582	1.50	<0.005		0.001
	169.00	170.50	D022583	1.50	<0.005		0.001
	170.50	172.00	D022584	1.50	<0.005		0.001
	172.00	173.50	D022586	1.50	<0.005		0.001
	173.50	175.00	D022587	1.50	<0.005		0.001
	175.00	176.50	D022588	1.50	<0.005		0.001
	176.50	178.00	D022589	1.50	<0.005		0.001
	178.00	179.50	D022590	1.50	<0.005		0.001
	179.50	181.00	D022591	1.50	<0.005		0.001
	181.00	182.50	D022592	1.50	<0.005		0.001
	182.50	184.00	D022593	1.50	<0.005		0.001
	184.00	185.50	D022594	1.50	<0.005		0.001
	185.50	187.00	D022596	1.50	0.006		0.006
	187.00	188.50	D022597	1.50	<0.005		0.001
	188.50	190.00	D022598	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
128.30	209.00	BA; AMY; MAS <b>Basalte; Amygdalaire; Roche massive</b> Basalte carbonaté, localement amygdalaire avec passage d'horizons tuffacés et graphiteux.	190.00	191.50	D022599	1.50	<0.005		0.001
			191.50	193.00	D022601	1.50	<0.005		0.001
			193.00	194.50	D022602	1.50	0.006		0.006
			194.50	196.00	D022603	1.50	<0.005		0.001
			196.00	197.50	D022604	1.50	0.005		0.005
			197.50	199.00	D022606	1.50	0.005		0.005
			199.00	200.50	D022607	1.50	<0.005		0.001
			200.50	202.00	D022608	1.50	<0.005		0.001
			202.00	203.50	D022609	1.50	0.007		0.007
			203.50	205.00	D022610	1.50	0.005		0.005
			205.00	206.50	D022611	1.50	0.005		0.005
			206.50	208.00	D022612	1.50	<0.005		0.001
			208.00	209.00	D022613	1.00	0.006		0.006
			128.30	130.00	D022551	1.70	0.008		0.008
			130.00	131.50	D022552	1.50	<0.005		0.001
			131.50	133.00	D022553	1.50	0.006		0.006
			133.00	134.50	D022554	1.50	0.008		0.008
			134.50	136.00	D022556	1.50	0.005		0.005
			136.00	137.50	D022557	1.50	0.006		0.006
			137.50	139.00	D022558	1.50	0.005		0.005
			139.00	140.50	D022559	1.50	<0.005		0.001
			140.50	142.20	D022561	1.70	0.006		0.006
			142.20	143.70	D022562	1.50	0.006		0.006
			143.70	145.00	D022563	1.30	0.005		0.005
			145.00	146.50	D022564	1.50	<0.005		0.001
			146.50	148.00	D022566	1.50	0.008		0.008
			148.00	149.00	D022567	1.00	<0.005		0.001
149.00	150.00	D022568	1.00	<0.005		0.001			
150.00	151.40	D022569	1.40	0.005		0.005			
151.40	153.00	D022570	1.60	0.005		0.005			
153.00	154.00	D022571	1.00	0.006		0.006			
154.00	155.50	D022572	1.50	<0.005		0.001			
155.50	157.00	D022573	1.50	0.005		0.005			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	157.00	158.50	D022574	1.50	0.005		0.005
	158.50	160.00	D022576	1.50	0.005		0.005
	160.00	161.50	D022577	1.50	0.005		0.005
	161.50	163.00	D022578	1.50	0.006		0.006
	163.00	164.50	D022579	1.50	<0.005		0.001
	164.50	166.00	D022580	1.50	<0.005		0.001
	166.00	167.50	D022581	1.50	<0.005		0.001
	167.50	169.00	D022582	1.50	<0.005		0.001
	169.00	170.50	D022583	1.50	<0.005		0.001
	170.50	172.00	D022584	1.50	<0.005		0.001
	172.00	173.50	D022586	1.50	<0.005		0.001
	173.50	175.00	D022587	1.50	<0.005		0.001
	175.00	176.50	D022588	1.50	<0.005		0.001
	176.50	178.00	D022589	1.50	<0.005		0.001
	178.00	179.50	D022590	1.50	<0.005		0.001
	179.50	181.00	D022591	1.50	<0.005		0.001
	181.00	182.50	D022592	1.50	<0.005		0.001
	182.50	184.00	D022593	1.50	<0.005		0.001
	184.00	185.50	D022594	1.50	<0.005		0.001
	185.50	187.00	D022596	1.50	0.006		0.006
	187.00	188.50	D022597	1.50	<0.005		0.001
	188.50	190.00	D022598	1.50	<0.005		0.001
	190.00	191.50	D022599	1.50	<0.005		0.001
	191.50	193.00	D022601	1.50	<0.005		0.001
	193.00	194.50	D022602	1.50	0.006		0.006
	194.50	196.00	D022603	1.50	<0.005		0.001
	196.00	197.50	D022604	1.50	0.005		0.005
	197.50	199.00	D022606	1.50	0.005		0.005
	199.00	200.50	D022607	1.50	<0.005		0.001
	200.50	202.00	D022608	1.50	<0.005		0.001
	202.00	203.50	D022609	1.50	0.007		0.007
	203.50	205.00	D022610	1.50	0.005		0.005
	205.00	206.50	D022611	1.50	0.005		0.005



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
209.00	218.00	ST <b>Siltstone</b> Siltstone carbonaté avec passages de veinules et injections graphiteux.	206.50	208.00	D022612	1.50	<0.005		0.001
			208.00	209.00	D022613	1.00	0.006		0.006
			209.00	210.50	D022614	1.50	0.008		0.008
			210.50	212.00	D022616	1.50	0.007		0.007
			212.00	213.50	D022617	1.50	<0.005		0.001
			213.50	215.00	D022618	1.50	0.014		0.014
			215.00	216.50	D022619	1.50	0.005		0.005
209.00	218.00	ST <b>Siltstone</b> Siltstone carbonaté avec passages de veinules et injections graphiteux.	216.50	218.00	D022620	1.50	0.006		0.006
			209.00	210.50	D022614	1.50	0.008		0.008
			210.50	212.00	D022616	1.50	0.007		0.007
			212.00	213.50	D022617	1.50	<0.005		0.001
			213.50	215.00	D022618	1.50	0.014		0.014
			215.00	216.50	D022619	1.50	0.005		0.005
218.00	321.00	BA; MAS <b>Basalte; Roche massive</b> Massive à gf, localement séricitisé avec cheveux et injections de matériel graphiteux.	216.50	218.00	D022620	1.50	0.006		0.006
			218.00	219.00	D022621	1.00	0.008		0.008
			219.00	220.50	D022622	1.50	<0.005		0.001
			220.50	222.00	D022623	1.50	0.006		0.006
			222.00	223.00	D022624	1.00	<0.005		0.001
			223.00	224.00	D022626	1.00	<0.005		0.001
			225.00	226.50	D022627	1.50	<0.005		0.001
			226.50	228.00	D022628	1.50	<0.005		0.001
			228.00	229.50	D022629	1.50	0.005		0.005
			229.50	231.00	D022630	1.50	<0.005		0.001
			231.00	232.50	D022631	1.50	0.005		0.005
			232.50	234.00	D022632	1.50	<0.005		0.001
			234.00	235.50	D022633	1.50	<0.005		0.001
			235.50	237.00	D022634	1.50	<0.005		0.001
			237.00	238.50	D022636	1.50	<0.005		0.001
			238.50	240.00	D022637	1.50	<0.005		0.001
240.00	241.50	D022638	1.50	0.005		0.005			
241.50	243.00	D022639	1.50	<0.005		0.001			
243.00	244.50	D022641	1.50	<0.005		0.001			
244.50	246.00	D022642	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.00	247.50	D022643	1.50	<0.005		0.001
	247.50	249.00	D022644	1.50	<0.005		0.001
	249.00	250.50	D022646	1.50	0.006		0.006
	250.50	252.00	D022647	1.50	<0.005		0.001
	252.00	253.50	D022648	1.50	0.005		0.005
	253.50	255.00	D022649	1.50	<0.005		0.001
	255.00	256.50	D022650	1.50	<0.005		0.001
	256.50	258.00	D022651	1.50	<0.005		0.001
	258.00	259.00	D022652	1.00	<0.005		0.001
	259.00	260.00	D022653	1.00	<0.005		0.001
	260.00	261.50	D022654	1.50	0.007		0.007
	261.50	263.00	D022656	1.50	0.042		0.042
	263.00	264.50	D022657	1.50	0.010		0.010
	264.50	266.00	D022658	1.50	<0.005		0.001
	266.00	267.50	D022659	1.50	<0.005		0.001
	267.50	269.00	D022660	1.50	<0.005		0.001
	269.00	270.50	D022661	1.50	<0.005		0.001
	270.50	272.00	D022662	1.50	<0.005		0.001
	272.00	273.50	D022663	1.50	<0.005		0.001
	273.50	275.00	D022664	1.50	0.007		0.007
	275.00	276.70	D022666	1.70	0.005		0.005
	276.70	278.00	D022667	1.30	0.207		0.207
	278.00	279.50	D022668	1.50	<0.005		0.001
	279.50	281.00	D022669	1.50	<0.005		0.001
	281.00	282.50	D022670	1.50	<0.005		0.001
	282.50	284.00	D022671	1.50	0.016		0.016
	284.00	285.50	D022672	1.50	<0.005		0.001
	285.50	287.00	D022673	1.50	<0.005		0.001
	287.00	288.50	D022674	1.50	<0.005		0.001
	288.50	290.00	D022676	1.50	<0.005		0.001
	290.00	291.50	D022677	1.50	0.005		0.005
	291.50	293.00	D022678	1.50	<0.005		0.001
	293.00	294.50	D022679	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
218.00	321.00	BA; MAS <b>Basalte; Roche massive</b> Massive à gf, localement séricitisé avec cheveux et injections de matériel graphiteux.	294.50	296.00	D022681	1.50	<0.005		0.001
			296.00	297.50	D022682	1.50	0.006		0.006
			297.50	299.00	D022683	1.50	<0.005		0.001
			299.00	300.50	D022684	1.50	0.007		0.007
			300.50	302.00	D022686	1.50	<0.005		0.001
			302.00	303.50	D022687	1.50	<0.005		0.001
			303.50	305.00	D022688	1.50	0.006		0.006
			305.00	306.50	D022689	1.50	<0.005		0.001
			306.50	308.00	D022690	1.50	0.012		0.012
			308.00	309.50	D022691	1.50	0.013		0.013
			309.50	311.00	D022692	1.50	0.181		0.181
			311.00	312.50	D022693	1.50	<0.005		0.001
			312.50	314.00	D022694	1.50	<0.005		0.001
			314.00	315.50	D022696	1.50	<0.005		0.001
			315.50	317.00	D022697	1.50	<0.005		0.001
			317.00	318.50	D022698	1.50	<0.005		0.001
			318.50	320.00	D022699	1.50	<0.005		0.001
			320.00	321.00	D022700	1.00	<0.005		0.001
			218.00	219.00	D022621	1.00	0.008		0.008
			219.00	220.50	D022622	1.50	<0.005		0.001
			220.50	222.00	D022623	1.50	0.006		0.006
			222.00	223.00	D022624	1.00	<0.005		0.001
			223.00	224.00	D022626	1.00	<0.005		0.001
			225.00	226.50	D022627	1.50	<0.005		0.001
			226.50	228.00	D022628	1.50	<0.005		0.001
			228.00	229.50	D022629	1.50	0.005		0.005
			229.50	231.00	D022630	1.50	<0.005		0.001
			231.00	232.50	D022631	1.50	0.005		0.005
			232.50	234.00	D022632	1.50	<0.005		0.001
			234.00	235.50	D022633	1.50	<0.005		0.001
235.50	237.00	D022634	1.50	<0.005		0.001			
237.00	238.50	D022636	1.50	<0.005		0.001			
238.50	240.00	D022637	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	240.00	241.50	D022638	1.50	0.005		0.005
	241.50	243.00	D022639	1.50	<0.005		0.001
	243.00	244.50	D022641	1.50	<0.005		0.001
	244.50	246.00	D022642	1.50	<0.005		0.001
	246.00	247.50	D022643	1.50	<0.005		0.001
	247.50	249.00	D022644	1.50	<0.005		0.001
	249.00	250.50	D022646	1.50	0.006		0.006
	250.50	252.00	D022647	1.50	<0.005		0.001
	252.00	253.50	D022648	1.50	0.005		0.005
	253.50	255.00	D022649	1.50	<0.005		0.001
	255.00	256.50	D022650	1.50	<0.005		0.001
	256.50	258.00	D022651	1.50	<0.005		0.001
	258.00	259.00	D022652	1.00	<0.005		0.001
	259.00	260.00	D022653	1.00	<0.005		0.001
	260.00	261.50	D022654	1.50	0.007		0.007
	261.50	263.00	D022656	1.50	0.042		0.042
	263.00	264.50	D022657	1.50	0.010		0.010
	264.50	266.00	D022658	1.50	<0.005		0.001
	266.00	267.50	D022659	1.50	<0.005		0.001
	267.50	269.00	D022660	1.50	<0.005		0.001
	269.00	270.50	D022661	1.50	<0.005		0.001
	270.50	272.00	D022662	1.50	<0.005		0.001
	272.00	273.50	D022663	1.50	<0.005		0.001
	273.50	275.00	D022664	1.50	0.007		0.007
	275.00	276.70	D022666	1.70	0.005		0.005
	276.70	278.00	D022667	1.30	0.207		0.207
	278.00	279.50	D022668	1.50	<0.005		0.001
	279.50	281.00	D022669	1.50	<0.005		0.001
	281.00	282.50	D022670	1.50	<0.005		0.001
	282.50	284.00	D022671	1.50	0.016		0.016
	284.00	285.50	D022672	1.50	<0.005		0.001
	285.50	287.00	D022673	1.50	<0.005		0.001
	287.00	288.50	D022674	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	288.50	290.00	D022676	1.50	<0.005		0.001	
	290.00	291.50	D022677	1.50	0.005		0.005	
	291.50	293.00	D022678	1.50	<0.005		0.001	
	293.00	294.50	D022679	1.50	0.005		0.005	
	294.50	296.00	D022681	1.50	<0.005		0.001	
	296.00	297.50	D022682	1.50	0.006		0.006	
	297.50	299.00	D022683	1.50	<0.005		0.001	
	299.00	300.50	D022684	1.50	0.007		0.007	
	300.50	302.00	D022686	1.50	<0.005		0.001	
	302.00	303.50	D022687	1.50	<0.005		0.001	
	303.50	305.00	D022688	1.50	0.006		0.006	
	305.00	306.50	D022689	1.50	<0.005		0.001	
	306.50	308.00	D022690	1.50	0.012		0.012	
	308.00	309.50	D022691	1.50	0.013		0.013	
	309.50	311.00	D022692	1.50	0.181		0.181	
	311.00	312.50	D022693	1.50	<0.005		0.001	
	312.50	314.00	D022694	1.50	<0.005		0.001	
	314.00	315.50	D022696	1.50	<0.005		0.001	
	315.50	317.00	D022697	1.50	<0.005		0.001	
	317.00	318.50	D022698	1.50	<0.005		0.001	
	318.50	320.00	D022699	1.50	<0.005		0.001	
	320.00	321.00	D022700	1.00	<0.005		0.001	
321.00	350.00	TU	321.00	322.50	D022701	1.50	<0.005	0.001
		<b>Tuf à blocs mafique</b>	322.50	324.00	D022702	1.50	<0.005	0.001
		Tuf à blocs mafique, localement fragment de QZ, laminations,	324.00	325.50	D022703	1.50	0.006	0.006
		localement altéré en calcite , PY en amas automorphe et fine diss	325.50	327.00	D022704	1.50	<0.005	0.001
			327.00	328.50	D022706	1.50	<0.005	0.001
			328.50	330.00	D022707	1.50	<0.005	0.001
			330.00	331.50	D022708	1.50	<0.005	0.001
			331.50	333.00	D022709	1.50	<0.005	0.001
			333.00	334.50	D022710	1.50	<0.005	0.001
			334.50	336.00	D022711	1.50	<0.005	0.001
			336.00	337.50	D022712	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
321.00	350.00	TU <b>Tuf à blocs mafique</b> Tuf à blocs mafique, localement fragment de QZ, laminations, localement altéré en calcite , PY en amas automorphe et fine diss	337.50	339.00	D022713	1.50	<0.005		0.001
			339.00	340.50	D022714	1.50	<0.005		0.001
			340.50	342.00	D022716	1.50	0.021		0.021
			342.00	343.50	D022717	1.50	<0.005		0.001
			343.50	345.00	D022718	1.50	<0.005		0.001
			345.00	346.50	D022719	1.50	<0.005		0.001
			346.50	348.00	D022721	1.50	<0.005		0.001
			348.00	349.00	D022722	1.00	<0.005		0.001
			349.00	350.00	D022723	1.00	0.005		0.005
			321.00	322.50	D022701	1.50	<0.005		0.001
			322.50	324.00	D022702	1.50	<0.005		0.001
			324.00	325.50	D022703	1.50	0.006		0.006
			325.50	327.00	D022704	1.50	<0.005		0.001
			327.00	328.50	D022706	1.50	<0.005		0.001
			328.50	330.00	D022707	1.50	<0.005		0.001
			330.00	331.50	D022708	1.50	<0.005		0.001
			331.50	333.00	D022709	1.50	<0.005		0.001
			333.00	334.50	D022710	1.50	<0.005		0.001
			334.50	336.00	D022711	1.50	<0.005		0.001
			336.00	337.50	D022712	1.50	<0.005		0.001
			337.50	339.00	D022713	1.50	<0.005		0.001
339.00	340.50	D022714	1.50	<0.005		0.001			
340.50	342.00	D022716	1.50	0.021		0.021			
342.00	343.50	D022717	1.50	<0.005		0.001			
343.50	345.00	D022718	1.50	<0.005		0.001			
345.00	346.50	D022719	1.50	<0.005		0.001			
346.50	348.00	D022721	1.50	<0.005		0.001			
348.00	349.00	D022722	1.00	<0.005		0.001			
349.00	350.00	D022723	1.00	0.005		0.005			
350.00	<b>Fin du sondage</b> Nombre d'échantillons : 211 Nombre d'échantillons QAQC : 30 Longueur totale échantillonnée : 310.20								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
43.00	44.50	D022485	D022484	1.50	0.005	0.005
53.50	53.50	D022495	L	0.00	2.110	2.110
67.00	68.50	D022505	D022504	1.50	<0.005	0.001
80.50	80.50	D022515	M	0.00	3.100	3.100
86.50	86.50	D022520	M1	0.00	<0.005	0.001
92.50	94.00	D022525	D022524	1.50	<0.005	0.001
106.00	106.00	D022535	J	0.00	0.777	0.777
119.50	121.00	D022545	D022544	1.50	<0.005	0.001
133.00	133.00	D022555	L	0.00	2.190	2.190
139.00	139.00	D022560	M1	0.00	<0.005	0.001
145.00	146.50	D022565	D022564	1.50	0.005	0.005
157.00	157.00	D022575	J	0.00	0.769	0.769
170.50	172.00	D022585	D022584	1.50	<0.005	0.001
184.00	184.00	D022595	K	0.00	0.952	0.952
190.00	190.00	D022600	M1	0.00	<0.005	0.001
196.00	197.50	D022605	D022604	1.50	0.005	0.005
209.00	209.00	D022615	L	0.00	2.140	2.140
222.00	223.00	D022625	D022624	1.00	<0.005	0.001
235.50	235.50	D022635	M	0.00	2.950	2.950
241.50	241.50	D022640	M1	0.00	<0.005	0.001
247.50	249.00	D022645	D022644	1.50	<0.005	0.001
260.00	260.00	D022655	J	0.00	0.763	0.763
273.50	275.00	D022665	D022664	1.50	<0.005	0.001
287.00	287.00	D022675	M	0.00	3.330	3.330
293.00	293.00	D022680	M1	0.00	<0.005	0.001
299.00	300.50	D022685	D022684	1.50	<0.005	0.001
312.50	312.50	D022695	J	0.00	0.678	0.678
325.50	327.00	D022705	D022704	1.50	<0.005	0.001
339.00	339.00	D022715	K	0.00	1.045	1.045
345.00	345.00	D022720	M1	0.00	0.008	0.008

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-192**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Johan Bergé

Lot :

Du :                              2010-04-29

Date de description :

Au :                              2010-05-04

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -68.00°  
 Longueur :                      353.00 m

Est	629 900.0
Nord	5 374 200.0
Élévation	279.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	14.00	0.00°	0.00°	Oui
Reflex	17.00	340.30°	-67.80°	Oui
Reflex	20.00	347.00°	-67.70°	Oui
Reflex	23.00	306.90°	-67.60°	Oui
Reflex	26.00	9.30°	-66.70°	Oui
Reflex	29.00	311.90°	-66.70°	Oui
Reflex	32.00	336.30°	-66.80°	Oui
Reflex	35.00	304.10°	-65.90°	Oui
Reflex	38.00	357.40°	-65.00°	Oui
Reflex	41.00	350.90°	-64.60°	Non
Reflex	44.00	352.40°	-65.40°	Non
Reflex	47.00	352.20°	-65.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	50.00	352.00°	-65.40°	Non
Reflex	53.00	351.50°	-65.50°	Non
Reflex	56.00	350.90°	-65.60°	Non
Reflex	59.00	350.40°	-65.60°	Non
Reflex	62.00	350.30°	-65.50°	Non
Reflex	65.00	349.90°	-65.50°	Non
Reflex	68.00	349.50°	-65.50°	Non
Reflex	71.00	349.20°	-65.40°	Non
Reflex	74.00	348.90°	-65.40°	Non
Reflex	77.00	348.10°	-65.30°	Non
Reflex	80.00	344.70°	-65.30°	Oui
Reflex	83.00	348.10°	-65.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	34.60	MT <b>Mort-terrain</b> No recovery.							
34.60	220.80	GA <b>Gabbro 40°</b> Unité de gabbro carbonaté et chloritisé. Non magnétique. Couleur gris verdâtre. Présence de leucoxène. Schistosité bien développé lié au cisaillement. La fuschite est très présente dans cette unité et est contenue dans des veines sur les 100 premiers mètres. L'unité contient des cheveux/veinule/veine de quartz et/ou carbonate. La pyrite est présente sous forme disséminée, et en amas de cristaux automorphes.	34.60	36.00	D031150	1.40	0.088		0.088
			36.00	37.50	D031151	1.50	0.046		0.046
			37.50	39.00	D031152	1.50	0.594		0.594
			39.00	40.50	D031154	1.50	0.285		0.285
			40.50	42.00	D031155	1.50	0.296		0.296
			42.00	43.50	D031156	1.50	0.246		0.246
			43.50	45.00	D031157	1.50	0.063		0.063
			45.00	46.50	D031158	1.50	0.522		0.522
			46.50	48.00	D031159	1.50	0.535		0.535
			48.00	49.50	D031160	1.50	0.249		0.249
			49.50	51.00	D031161	1.50	2.050		2.050
			51.00	52.50	D031162	1.50	0.628		0.628
			52.50	54.00	D031164	1.50	0.126		0.126
			54.00	55.50	D031165	1.50	<0.005		0.001
			55.50	57.00	D031166	1.50	0.007		0.007
			57.00	58.50	D031167	1.50	<0.005		0.001
			58.50	60.00	D031168	1.50	0.005		0.005
			60.00	61.50	D031169	1.50	<0.005		0.001
			61.50	63.00	D031171	1.50	<0.005		0.001
			63.00	64.50	D031172	1.50	<0.005		0.001
			64.50	66.00	D031174	1.50	<0.005		0.001
			66.00	67.50	D031175	1.50	<0.005		0.001
			67.50	69.00	D031176	1.50	<0.005		0.001
			69.00	70.50	D031177	1.50	<0.005		0.001
			70.50	72.00	D031178	1.50	<0.005		0.001
			72.00	73.50	D031179	1.50	<0.005		0.001
			73.50	75.00	D031180	1.50	<0.005		0.001
			75.00	76.00	D031181	1.00	<0.005		0.001
			76.00	77.00	D031182	1.00	<0.005		0.001
			77.00	78.20	D031184	1.20	<0.005		0.001
			78.20	79.80	D031185	1.60	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	79.80	81.50	D031186	1.70	<0.005		0.001
	81.50	83.00	D031187	1.50	<0.005		0.001
	83.00	84.50	D031188	1.50	<0.005		0.001
	84.50	86.00	D031189	1.50	<0.005		0.001
	86.00	87.50	D031190	1.50	<0.005		0.001
	87.50	89.00	D031191	1.50	<0.005		0.001
	89.00	90.50	D031192	1.50	<0.005		0.001
	90.50	92.00	D031194	1.50	<0.005		0.001
	92.00	93.50	D031195	1.50	<0.005		0.001
	93.50	95.00	D031196	1.50	<0.005		0.001
	95.00	96.50	D031197	1.50	<0.005		0.001
	96.50	98.00	D031198	1.50	<0.005		0.001
	98.00	99.50	D031199	1.50	<0.005		0.001
	99.50	101.00	D031200	1.50	<0.005		0.001
	101.00	102.50	D031201	1.50	<0.005		0.001
	102.50	104.00	D031202	1.50	<0.005		0.001
	104.00	105.50	D031204	1.50	<0.005		0.001
	105.50	107.00	D031205	1.50	<0.005		0.001
	107.00	108.50	D031206	1.50	<0.005		0.001
	108.50	110.00	D031207	1.50	<0.005		0.001
	110.00	111.50	D031208	1.50	<0.005		0.001
	111.50	113.00	D031209	1.50	<0.005		0.001
	113.00	114.50	D031211	1.50	<0.005		0.001
	114.50	116.00	D031212	1.50	<0.005		0.001
	116.00	117.50	D031214	1.50	<0.005		0.001
	117.50	119.00	D031215	1.50	<0.005		0.001
	119.00	120.50	D031216	1.50	<0.005		0.001
	120.50	122.00	D031217	1.50	<0.005		0.001
	122.00	123.50	D031218	1.50	<0.005		0.001
	123.50	125.00	D031219	1.50	<0.005		0.001
	125.00	126.50	D031220	1.50	<0.005		0.001
	126.50	128.00	D031221	1.50	<0.005		0.001
	128.00	129.50	D031222	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			129.50	131.00	D031224	1.50	<0.005		0.001
			131.00	132.50	D031225	1.50	<0.005		0.001
			132.50	134.00	D031226	1.50	<0.005		0.001
			134.00	135.50	D031227	1.50	<0.005		0.001
			135.50	137.00	D031228	1.50	<0.005		0.001
			137.00	138.50	D031229	1.50	<0.005		0.001
			138.50	140.00	D031230	1.50	<0.005		0.001
			140.00	141.50	D031231	1.50	<0.005		0.001
			141.50	143.00	D031232	1.50	<0.005		0.001
			143.00	144.50	D031234	1.50	<0.005		0.001
			144.50	146.00	D031235	1.50	<0.005		0.001
			146.00	147.50	D031236	1.50	<0.005		0.001
			147.50	149.00	D031237	1.50	<0.005		0.001
			149.00	150.50	D031238	1.50	<0.005		0.001
			150.50	152.00	D031239	1.50	<0.005		0.001
			152.00	153.50	D031240	1.50	<0.005		0.001
			153.50	155.00	D031241	1.50	<0.005		0.001
			155.00	156.50	D031242	1.50	<0.005		0.001
			156.50	158.00	D031244	1.50	<0.005		0.001
			158.00	159.50	D031245	1.50	<0.005		0.001
			159.50	161.00	D031246	1.50	<0.005		0.001
			161.00	162.50	D031247	1.50	<0.005		0.001
			162.50	164.00	D031248	1.50	<0.005		0.001
34.60	66.00	GA <b>Gabbro 40°</b> Gabbro cisailé très chloritisé et peu carbonaté. Présence de clastes de gabbro carbonaté(à grain moyen) moulés dans la matrice de granulo très fine carbonatée en général.							
34.60	66.00	CIS <b>Cisaillement 45°</b> Cisaillement qui affecte et altère toute l'unité gabbroïque. La direction varie, moyenne à 45°. Ce cisaillement diminue la granulo du gabbro, seul quelques reliques ne sont pas affectées (grain moyen).							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
163.90	170.30	<p>V ca;2 cm;;;30°;;</p> <p><b>Veine de calcite 2 cm 30°</b></p> <p>Veine à matrice carbonaté qui porte des cristaux de quartz gris subautomorphe.</p> <p>Texture brechique.</p> <p>Minéralisation en pyrite importante.</p> <p>Il s'agit plutot d'un réseau de veines parallèles à 30' qui se répète dans toute la zone.</p>	164.00	165.50	D031249	1.50	<0.005		0.001
			165.50	167.00	D031251	1.50	<0.005		0.001
			167.00	168.50	D031252	1.50	<0.005		0.001
			168.50	170.00	D031254	1.50	<0.005		0.001
			170.00	171.50	D031255	1.50	<0.005		0.001
			171.50	173.00	D031256	1.50	<0.005		0.001
			173.00	174.50	D031257	1.50	<0.005		0.001
			174.50	176.00	D031258	1.50	<0.005		0.001
			176.00	177.50	D031259	1.50	<0.005		0.001
			177.50	179.00	D031260	1.50	<0.005		0.001
			179.00	180.50	D031261	1.50	<0.005		0.001
			180.50	182.00	D031262	1.50	0.007		0.007
180.90	181.90	<p>V ca;1 cm;;;5°;;</p> <p><b>Veine de calcite 1 cm 5°</b></p> <p>Veine à matrice carbonaté avec quartz.</p> <p>Pyrite disséminée très finement et amas de cristaux automorphes.</p>	182.00	183.50	D031264	1.50	<0.005		0.001
			183.50	185.00	D031265	1.50	<0.005		0.001
			185.00	186.50	D031266	1.50	<0.005		0.001
			186.50	188.00	D031267	1.50	<0.005		0.001
187.70	188.70	<p>V ca;1 cm;;;5°;;</p> <p><b>Veine de calcite 1 cm 5°</b></p> <p>Veine à matrice carbonatée et riche en quartz.</p> <p>Minéralisation en pyrite importante.</p>	188.00	189.50	D031268	1.50	<0.005		0.001
			189.50	191.00	D031269	1.50	<0.005		0.001
			191.00	192.50	D031270	1.50	<0.005		0.001
			192.50	194.00	D031271	1.50	<0.005		0.001
			194.00	195.50	D031272	1.50	<0.005		0.001
			195.50	197.00	D031274	1.50	<0.005		0.001
			197.00	198.50	D031275	1.50	<0.005		0.001
197.30	199.20	<p>FRC</p> <p><b>Fracturé 5°</b></p> <p>Fracture verticale.</p> <p>Chloritisée et carbonatée.</p>	198.50	200.00	D031276	1.50	<0.005		0.001
			200.00	201.50	D031277	1.50	<0.005		0.001
			201.50	203.00	D031278	1.50	<0.005		0.001
			203.00	204.50	D031279	1.50	<0.005		0.001
			204.50	205.90	D031280	1.40	<0.005		0.001
			205.90	207.50	D031281	1.60	<0.005		0.001
			207.50	209.00	D031282	1.50	<0.005		0.001
			209.00	210.50	D031284	1.50	<0.005		0.001
			210.50	212.00	D031285	1.50	<0.005		0.001
			212.00	213.50	D031286	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
220.80	221.00	NR  <b>Carotte perdue</b> 20 cm de carotte perdue (zone fracturée).	213.50	215.00	D031287	1.50	<0.005		0.001
			215.00	216.50	D031288	1.50	<0.005		0.001
			216.50	218.00	D031289	1.50	<0.005		0.001
			218.00	219.50	D031291	1.50	<0.005		0.001
			219.50	220.80	D031292	1.30	<0.005		0.001
221.00	230.80	GA  <b>Gabbro 25°</b> Unité de gabbro carbonaté et chloritisé. Non magnétique. Couleur gris verdâtre. Présence de leucoxène. Schistosité bien développé lié au cisaillement. L'unité contient des cheveux/veinule/veine de quartz et/ou carbonate. La pyrite est présente sous forme disséminée, et en amas de cristaux automorphes.	221.00	222.50	D031294	1.50	<0.005		0.001
			222.50	224.00	D031295	1.50	<0.005		0.001
			224.00	225.50	D031296	1.50	<0.005		0.001
			225.50	227.00	D031297	1.50	<0.005		0.001
			227.00	228.50	D031298	1.50	<0.005		0.001
			228.50	229.80	D031299	1.30	<0.005		0.001
			229.80	230.80	D031300	1.00	<0.005		0.001
			230.80	273.00	TU  <b>Tuf à blocs mafique 0°</b> Tuf de granulométrie très fine. Couleur gris sombre à gris verdâtre: altération en chlorite. Présence de lit de graphite, avec granoclasement par endroit. L'unité est non carbonatée. Le réseau de veine de quartz carbonate est bien développé. Minéralisation en pyrite peu développée, et contenue dans les veines de quartz carbonates et les lits de graphites. Ici on voit clairement deux unités de tuf à bloc felsiques le contact est à 259.40 avec un angle de 20°. L'unité inférieure est carbonatée.	230.80	232.50	D031301	1.70
232.50	234.00	D031302				1.50	<0.005		0.001
234.00	235.50	D031304				1.50	<0.005		0.001
235.50	237.00	D031305				1.50	<0.005		0.001
237.00	238.50	D031306				1.50	0.006		0.006
238.50	240.00	D031307				1.50	0.005		0.005
240.00	241.50	D031308				1.50	<0.005		0.001
241.50	243.00	D031309				1.50	<0.005		0.001
243.00	244.50	D031310				1.50	<0.005		0.001
244.50	246.00	D031311				1.50	<0.005		0.001
246.00	247.50	D031312				1.50	<0.005		0.001
247.50	249.00	D031314				1.50	<0.005		0.001
249.00	250.50	D031315				1.50	<0.005		0.001
250.50	252.00	D031316				1.50	<0.005		0.001
252.00	253.50	D031317				1.50	<0.005		0.001
253.50	255.00	D031318	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
273.00	318.00	BA <b>Basalte 90°</b> Basalte carbonaté, avec passages décimétriques non carbonatés. L'unité est limité à sa base par une veine de quartz. Le basalte présente une schistosité bien développé. La minéralisation en pyrite est très faible dans cette unité.	255.00	256.50	D031319	1.50	<0.005		0.001
			256.50	258.00	D031320	1.50	<0.005		0.001
			258.00	259.50	D031321	1.50	<0.005		0.001
			259.50	261.00	D031322	1.50	0.006		0.006
			261.00	262.50	D031324	1.50	0.005		0.005
			262.50	264.00	D031325	1.50	<0.005		0.001
			264.00	265.50	D031326	1.50	0.008		0.008
			265.50	267.00	D031327	1.50	0.008		0.008
			267.00	268.50	D031328	1.50	0.007		0.007
			268.50	270.00	D031329	1.50	<0.005		0.001
			270.00	271.50	D031331	1.50	<0.005		0.001
			271.50	273.00	D031332	1.50	<0.005		0.001
			273.00	274.50	D031334	1.50	<0.005		0.001
			274.50	276.00	D031335	1.50	0.006		0.006
			276.00	277.50	D031336	1.50	<0.005		0.001
			277.50	279.00	D031337	1.50	0.005		0.005
			279.00	280.50	D031338	1.50	<0.005		0.001
			280.50	282.00	D031339	1.50	<0.005		0.001
			282.00	283.50	D031340	1.50	<0.005		0.001
			283.50	285.00	D031341	1.50	0.007		0.007
			285.00	286.50	D031342	1.50	<0.005		0.001
			286.50	288.00	D031344	1.50	<0.005		0.001
			288.00	289.10	D031345	1.10	<0.005		0.001
			289.10	290.50	D031346	1.40	<0.005		0.001
			290.50	292.10	D031347	1.60	<0.005		0.001
			292.10	293.50	D031348	1.40	<0.005		0.001
			293.50	295.00	D031349	1.50	<0.005		0.001
			295.00	296.50	D031350	1.50	<0.005		0.001
			296.50	298.00	D031351	1.50	0.005		0.005
			298.00	299.50	D031352	1.50	<0.005		0.001
299.50	301.00	D031354	1.50	<0.005		0.001			
301.00	302.50	D031355	1.50	<0.005		0.001			
302.50	304.00	D031356	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			304.00	304.80	D031357	0.80	<0.005		0.001
			304.80	306.00	D031358	1.20	<0.005		0.001
			306.00	307.00	D031359	1.00	<0.005		0.001
			307.00	308.50	D031360	1.50	<0.005		0.001
			308.50	310.20	D031361	1.70	0.007		0.007
			310.20	311.50	D031362	1.30	<0.005		0.001
			311.50	313.00	D031364	1.50	0.006		0.006
			313.00	314.50	D031365	1.50	0.006		0.006
313.40	314.30	QZVN <b>Veine de Quartz massive 40°</b> Veine de quartz carbonate qui recoupe le basalte et contient des fragments de basaltes altérés par la chlorite.							
314.30	315.30	UM <b>Ultramaïfite serpentinisée</b> Ultramaïfite avec lambeaux (spinifex) en bordure. Minéralisation en pentlandite.	314.50	316.00	D031366	1.50	0.006		0.006
			316.00	317.50	D031367	1.50	<0.005		0.001
			317.50	319.00	D031368	1.50	<0.005		0.001
318.00	353.00	GA <b>Gabbro</b> Gabbro carbonaté à passage non carbonaté.	319.00	320.50	D031369	1.50	<0.005		0.001
			320.50	321.80	D031371	1.30	0.018		0.018
			321.80	323.50	D031372	1.70	0.010		0.010
			323.50	325.00	D031374	1.50	<0.005		0.001
			325.00	326.50	D031375	1.50	<0.005		0.001
			326.50	328.00	D031376	1.50	0.006		0.006
			328.00	328.80	D031377	0.80	<0.005		0.001
			328.80	330.50	D031378	1.70	<0.005		0.001
			330.50	332.00	D031379	1.50	<0.005		0.001
332.00	353.00	GA <b>Gabbro 5°</b> Gabbro plus clair et plus grossier.	332.00	333.50	D031380	1.50	<0.005		0.001
			333.50	335.00	D031381	1.50	<0.005		0.001
			335.00	336.50	D031382	1.50	<0.005		0.001
			336.50	338.00	D031384	1.50	0.005		0.005
			338.00	339.50	D031385	1.50	<0.005		0.001
			339.50	341.00	D031386	1.50	<0.005		0.001
			341.00	342.50	D031387	1.50	0.005		0.005
			342.50	344.00	D031388	1.50	<0.005		0.001
			344.00	345.50	D031389	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D031390	1.50	<0.005		0.001
	347.00	348.50	D031391	1.50	<0.005		0.001
	348.50	350.00	D031392	1.50	<0.005		0.001
	350.00	351.50	D031394	1.50	0.005		0.005
	351.50	353.00	D031395	1.50	<0.005		0.001
353.00	Fin du sondage Nombre d'échantillons : 215 Nombre d'échantillons QAQC : 31 Longueur totale échantillonnée : 318.20						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
37.50	37.50	D031153	M	0.00	3.090	3.090
51.00	52.50	D031163	D031162	1.50	0.685	0.685
60.00	60.00	D031170	M1	0.00	<0.005	0.001
63.00	63.00	D031173	J	0.00	0.828	0.828
76.00	77.00	D031183	D031182	1.00	<0.005	0.001
89.00	89.00	D031193	K	0.00	1.055	1.055
102.50	104.00	D031203	D031202	1.50	<0.005	0.001
111.50	111.50	D031210	M1	0.00	<0.005	0.001
114.50	114.50	D031213	L	0.00	2.010	2.010
128.00	129.50	D031223	D031222	1.50	<0.005	0.001
141.50	141.50	D031233	M	0.00	3.160	3.160
155.00	156.50	D031243	D031242	1.50	<0.005	0.001
164.00	164.00	D031250	M1	0.00	<0.005	0.001
167.00	167.00	D031253	J	0.00	0.565	0.565
180.50	182.00	D031263	D031262	1.50	0.005	0.005
194.00	194.00	D031273	K	0.00	0.978	0.978
207.50	209.00	D031283	D031282	1.50	<0.005	0.001
216.50	216.50	D031290	M1	0.00	<0.005	0.001
219.50	219.50	D031293	L	0.00	2.130	2.130
232.50	234.00	D031303	D031302	1.50	<0.005	0.001
246.00	246.00	D031313	M	0.00	3.200	3.200
259.50	261.00	D031323	D031322	1.50	0.008	0.008
268.50	268.50	D031330	M1	0.00	<0.005	0.001
271.50	271.50	D031333	J	0.00	0.806	0.806
285.00	286.50	D031343	D031342	1.50	<0.005	0.001
298.00	298.00	D031353	K	0.00	1.000	1.000
310.20	311.50	D031363	D031362	1.30	0.050	0.050
319.00	319.00	D031370	M1	0.00	<0.005	0.001
321.80	321.80	D031373	L	0.00	2.200	2.200
335.00	336.50	D031383	D031382	1.50	<0.005	0.001
348.50	348.50	D031393	M	0.00	3.090	3.090

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-193**

Titre minier :

Section :                      630300

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Sylvain SAVADOGO

Lot :

Du :                      2010-04-27

Date de description :              2010-06-17

Au :                      2010-04-28

Collet

UTM

Azimut :                      353.00°

Est                              630 306.2

Plongée :                      -60.00°

Nord                              5 374 550.7

Longueur :                      61.70 m

Élévation                      295.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	332.70°	-60.10°	Oui
Reflex	8.00	332.60°	-60.10°	Oui
Reflex	11.00	332.80°	-60.00°	Oui
Reflex	14.00	344.20°	-60.10°	Oui
Reflex	17.00	346.10°	-60.10°	Oui
Reflex	20.00	356.90°	-60.20°	Non
Reflex	23.00	0.80°	-60.30°	Non
Reflex	26.00	3.80°	-60.10°	Non
Reflex	29.00	0.70°	-58.90°	Non
Reflex	32.00	1.30°	-60.00°	Non
Reflex	35.00	3.30°	-59.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.00°	-59.90°	Non
Reflex	41.00	3.10°	-59.90°	Non
Reflex	44.00	1.40°	-60.00°	Non
Reflex	47.00	355.70°	-46.70°	Oui
Reflex	50.00	0.20°	-56.60°	Non
Reflex	53.00	2.10°	-59.90°	Non
Reflex	56.00	2.10°	-59.80°	Non
Reflex	59.00	2.20°	-59.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	14.40	MT <b>Mort-terrain</b> MT							
14.40	61.70	SY; POR <b>Syénite 75°; Porphyrique</b> syénite porphyrique avec des cristaux moyens à grossiers (2mm-1cm) de feldspath arrondi ou autoomorphe; plus ou moins éa modérément carbonaté; fin cristaux de pyrite disséminé entre 0,2% et 0,5% dans la matrice;  De 14.4m à 54,30m, plus ou moins à modérément hématisé; De 14.4m à 26m, peu à plus ou moins chloritisé; De 54,3m à 61,7m, plus ou moins chloritisé	14.40	15.50	D034001	1.10	0.529		0.529
			15.50	17.00	D034002	1.50	0.157		0.157
			17.00	18.50	D034003	1.50	0.016		0.016
			18.50	20.00	D034004	1.50	0.008		0.008
			20.00	21.50	D034005	1.50	<0.005		0.001
14.40	26.00	CB05; CH03; HM <b>Carbonaté 5; Chloriteux 3; Hématisé</b> modérément carbonaté; peu à plus ou moins chloriteux; plus ou moins hématisé;							
21.50	24.50	Py01; AS01 <b>Pyrite 1%; Arsénopyrite 1%</b> cristaux fins de pyrite disséminé entre 0,2% et 0,5%; trace cristaux fin d'arsénopyrite;	21.50	23.00	D034006	1.50	<0.005		0.001
			23.00	24.50	D034007	1.50	<0.005		0.001
			24.50	26.00	D034008	1.50	<0.005		0.001
26.00	54.30	CB05; HM <b>Carbonaté 5; Hématisé</b> modérément carbonaté et modérément hématisé	26.00	27.50	D034009	1.50	<0.005		0.001
			27.50	29.00	D034011	1.50	<0.005		0.001
			29.00	30.50	D034012	1.50	<0.005		0.001
			30.50	32.00	D034013	1.50	<0.005		0.001
			32.00	33.50	D034014	1.50	<0.005		0.001
			33.50	35.00	D034015	1.50	0.039		0.039
			35.00	36.50	D034016	1.50	0.013		0.013
			36.50	38.00	D034017	1.50	0.020		0.020
			38.00	39.50	D034018	1.50	0.007		0.007
			39.50	41.00	D034019	1.50	<0.005		0.001
			41.00	42.50	D034021	1.50	<0.005		0.001
			42.50	44.00	D034022	1.50	0.019		0.019
			44.00	45.50	D034023	1.50	0.274		0.274
			45.50	47.00	D034024	1.50	0.018		0.018
			47.00	48.50	D034025	1.50	0.047		0.047
			48.50	50.00	D034026	1.50	0.097		0.097

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
54.30	61.70	CB05; CH03 <b>Carbonaté 5; Chloriteux 3</b> modérément carbonaté et plus ou moins chloriteux;	50.00	51.50	D034027	1.50	0.962		0.962
			51.50	53.00	D034028	1.50	0.887		0.887
			53.00	54.50	D034029	1.50	0.832		0.832
			54.50	56.00	D034031	1.50	1.000		1.000
			56.00	57.50	D034033	1.50	0.682		0.682
			57.50	59.00	D034034	1.50	0.684		0.684
59.00	60.50	Py01 <b>Pyrite 1%</b> cristaux de pyrite disséminé entre 0,5% et 0,8% dans la matrice et la zone de veines	59.00	60.50	D034035	1.50	0.950		0.950
			60.50	61.70	D034036	1.20	0.094		0.094
61.70	<b>Fin du sondage</b> Nombre d'échantillons : 32 Nombre d'échantillons QAQC : 4 Longueur totale échantillonnée : 47.30								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
26.00	26.00	D034010	J	0.00	0.770	0.770
39.50	41.00	D034020	D034019	1.50	<0.005	0.001
53.00	53.00	D034030	K	0.00	1.015	1.015
54.50	54.50	D034032	M1	0.00	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.30	MT <b>Mort-terrain</b> MT							
3.30	51.00	SY; POR <b>Syénite 30°; Porphyrique</b> syénite porphyrique avec des cristaux moyens à grossiers (2mm-1cm) de feldspath arrondi ou autoomorphe; plus ou moins éa modérément carbonaté; fin cristaux de pyrite disséminé à 0,2% dans la matrice et partiellement entre 0,2% et 0,5%;	3.30	5.00	D034037	1.70	0.054		0.054
			5.00	6.50	D034038	1.50	0.021		0.021
			6.50	8.00	D034039	1.50	<0.005		0.001
			8.00	9.50	D034041	1.50	<0.005		0.001
3.30	9.50	HM <b>Hématisé</b> modérément hématisé							
9.50	41.00	CB05; HM <b>Carbonaté 5; Hématisé</b> plus ou moins à modérément carbonaté, modérément hématisé; De 32,6m à 33,4m, plus ou moins chloritisé; De 35m à 39m, peu à plus ou moins chloritisé;	9.50	11.00	D034042	1.50	<0.005		0.001
			11.00	12.50	D034043	1.50	<0.005		0.001
			12.50	14.00	D034044	1.50	<0.005		0.001
			14.00	15.50	D034045	1.50	<0.005		0.001
			15.50	17.00	D034046	1.50	0.049		0.049
17.00	18.50	Py01 <b>Pyrite 1%</b> cristaux de pyrite disséminé entre 0,2% et 0,5%;	17.00	18.50	D034047	1.50	0.028		0.028
			18.50	20.00	D034048	1.50	<0.005		0.001
			20.00	21.50	D034049	1.50	0.014		0.014
			21.50	23.00	D034051	1.50	<0.005		0.001
			23.00	24.50	D034052	1.50	0.005		0.005
			24.50	26.00	D034053	1.50	0.044		0.044
			26.00	27.50	D034054	1.50	0.153		0.153
			27.50	29.00	D034055	1.50	0.010		0.010
			29.00	30.50	D034056	1.50	<0.005		0.001
			30.50	32.00	D034057	1.50	0.008		0.008
32.00	39.50	Py01 <b>Pyrite 1%</b> cristaux de pyrite entre 0,2% et 0,5% dans les zones CHSY;	32.00	33.50	D034058	1.50	0.240		0.240
			33.50	35.00	D034059	1.50	0.022		0.022
			35.00	36.50	D034061	1.50	0.051		0.051
			36.50	38.00	D034062	1.50	0.043		0.043
			38.00	39.50	D034063	1.50	0.007		0.007
			39.50	41.00	D034064	1.50	<0.005		0.001
41.00	44.00	CH02; HM <b>Chloriteux 2; Hématisé</b>	41.00	42.50	D034065	1.50	<0.005		0.001
			42.50	44.00	D034066	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
44.00	50.00	peu chloriteux et modérément hématisé; CB05; HM <b>Carbonaté 5; Hématisé</b> modérément carbonaté et modérément hématisée	44.00	45.50	D034067	1.50	<0.005		0.001
			45.50	47.00	D034068	1.50	<0.005		0.001
			47.00	48.50	D034069	1.50	0.014		0.014
			48.50	50.00	D034071	1.50	0.005		0.005
50.00	51.00	CB05; HM <b>Carbonaté 5; Hématisé</b> plus ou moins et modérément carbonaté; plus ou moins hématisé et plus ou moins chloritisé;	50.00	51.50	D034073	1.50	0.114		0.114
51.00	54.00	TU; GRO <b>Tuf à cendre/lapillis 40°; Grains grossiers</b> Tuff à lapilli; contenant des fragments arrondis de quartz-feldspath suivant une foliation à 40°AC; cristaux de pyrite disséminé jusqu'à 2% dans la matrice; peu à plus ou moins carbonaté; zone marquant la transition entre la syénite et le basalte;							
51.00	60.50	CB03 <b>Carbonaté 3</b> peu à plus ou moins carbonaté;	51.50	53.00	D034074	1.50	0.022		0.022
			53.00	54.50	D034075	1.50	0.106		0.106
54.00	182.00	BA <b>Basalte 40°</b> basalte peu à modérément carbonaté; folié partiellement; contenant des amygdules de quartz feldspath et des amygdules de calcite; pyrite disséminé dans la matrice et les veines de quartz-calcite;  Toutes les veines de quartz-calcite ne sont pas orientées; elles sont souvent en stockwork;  des rides de pillow ont été aussi observées;	54.50	56.00	D034076	1.50	<0.005		0.001
			56.00	57.50	D034077	1.50	<0.005		0.001
			57.50	59.00	D034078	1.50	<0.005		0.001
			59.00	60.50	D034079	1.50	<0.005		0.001
60.50	68.00	CB05 <b>Carbonaté 5</b> modérément carbonaté;	60.50	62.00	D034081	1.50	<0.005		0.001
			62.00	63.50	D034082	1.50	<0.005		0.001
			63.50	65.00	D034083	1.50	<0.005		0.001
			65.00	66.50	D034084	1.50	<0.005		0.001
			66.50	68.00	D034085	1.50	<0.005		0.001
68.00	182.00	CB04 <b>Carbonaté 4</b> plus ou moins à modérément carbonaté;	68.00	69.50	D034086	1.50	<0.005		0.001
			69.50	71.00	D034087	1.50	<0.005		0.001
			71.00	72.50	D034088	1.50	<0.005		0.001
			72.50	74.00	D034089	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
96.50	101.00	Py00.5 <b>Pyrite 0.5%</b> cristaux de pyrite disséminé entre 0,2% et 0,5% dans la matrice et les amygdules;	74.00	75.50	D034091	1.50	<0.005		0.001
			75.50	77.00	D034092	1.50	<0.005		0.001
			77.00	78.50	D034093	1.50	<0.005		0.001
			78.50	80.00	D034094	1.50	<0.005		0.001
			80.00	81.50	D034095	1.50	<0.005		0.001
			81.50	83.00	D034096	1.50	<0.005		0.001
			83.00	84.50	D034097	1.50	<0.005		0.001
			84.50	86.00	D034098	1.50	<0.005		0.001
			86.00	87.50	D034099	1.50	<0.005		0.001
			87.50	89.00	D034101	1.50	<0.005		0.001
			89.00	90.50	D034102	1.50	<0.005		0.001
			90.50	92.00	D034103	1.50	<0.005		0.001
			92.00	93.50	D034104	1.50	0.005		0.005
			93.50	95.00	D034105	1.50	<0.005		0.001
			95.00	96.50	D034106	1.50	<0.005		0.001
			96.50	98.00	D034107	1.50	<0.005		0.001
			98.00	99.50	D034108	1.50	0.011		0.011
			99.50	101.00	D034109	1.50	0.016		0.016
			101.00	102.50	D034111	1.50	0.007		0.007
			102.50	104.00	D034113	1.50	0.640		0.640
104.00	105.50	D034114	1.50	0.690		0.690			
105.50	107.00	D034115	1.50	0.012		0.012			
107.00	108.50	D034116	1.50	0.028		0.028			
108.50	110.00	D034117	1.50	0.025		0.025			
110.00	111.50	D034118	1.50	0.008		0.008			
111.50	113.00	D034119	1.50	0.011		0.011			
113.00	114.50	D034121	1.50	0.012		0.012			
114.50	116.00	D034122	1.50	<0.005		0.001			
116.00	117.50	D034123	1.50	0.005		0.005			
117.50	119.00	D034124	1.50	0.005		0.005			
119.00	120.50	D034125	1.50	0.006		0.006			
120.50	122.00	D034126	1.50	0.009		0.009			
122.00	123.50	D034127	1.50	0.343		0.343			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
et les amygdules;	123.50	125.00	D034128	1.50	0.137		0.137
	125.00	126.50	D034129	1.50	0.632		0.632
	126.50	128.00	D034131	1.50	0.009		0.009
	128.00	129.50	D034132	1.50	0.370		0.370
	129.50	131.00	D034133	1.50	0.429		0.429
	131.00	132.50	D034134	1.50	0.015		0.015
	132.50	134.00	D034135	1.50	0.013		0.013
	134.00	135.50	D034136	1.50	0.010		0.010
	135.50	137.00	D034137	1.50	0.005		0.005
	137.00	138.50	D034138	1.50	0.005		0.005
	138.50	140.00	D034139	1.50	0.005		0.005
	140.00	141.50	D034141	1.50	<0.005		0.001
	141.50	143.00	D034142	1.50	<0.005		0.001
	143.00	144.50	D034143	1.50	0.005		0.005
	144.50	146.00	D034144	1.50	0.011		0.011
	146.00	147.50	D034145	1.50	0.010		0.010
	147.50	149.00	D034146	1.50	0.006		0.006
	149.00	150.50	D034147	1.50	0.006		0.006
	150.50	152.00	D034148	1.50	0.005		0.005
	152.00	153.50	D034149	1.50	0.007		0.007
152.00	155.00	D034151	1.50	0.013		0.013	
155.00	156.50	D034153	1.50	0.005		0.005	
156.50	158.00	D034154	1.50	<0.005		0.001	
158.00	159.50	D034155	1.50	<0.005		0.001	
159.50	161.00	D034156	1.50	<0.005		0.001	
161.00	162.50	D034157	1.50	0.006		0.006	
162.50	164.00	D034158	1.50	<0.005		0.001	
164.00	165.50	D034159	1.50	<0.005		0.001	
165.50	167.00	D034161	1.50	<0.005		0.001	
167.00	168.50	D034162	1.50	0.482		0.482	
168.50	170.00	D034163	1.50	0.458		0.458	
170.00	171.50	D034164	1.50	0.010		0.010	
171.50	173.00	D034165	1.50	0.006		0.006	
152.00	155.00	Py00.5 <b>Pyrite 0.5%</b> cristaux de pyrite disséminé entre 0,2% et 0,5% dans la matrice et les amygdules;					

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	173.00	174.50	D034166	1.50	0.009		0.009
	174.50	176.00	D034167	1.50	0.407		0.407
	176.00	177.50	D034168	1.50	0.227		0.227
	177.50	179.00	D034169	1.50	<0.005		0.001
	179.00	180.50	D034171	1.50	<0.005		0.001
	180.50	182.00	D034172	1.50	0.010		0.010
182.00	Fin du sondage Nombre d'échantillons : 119 Nombre d'échantillons QAQC : 17 Longueur totale échantillonnée : 178.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.50	8.00	D034040	D034039	1.50	<0.005	0.001
20.00	20.00	D034050	M	0.00	2.970	2.970
33.50	35.00	D034060	D034059	1.50	0.020	0.020
47.00	47.00	D034070	J	0.00	0.762	0.762
48.50	48.50	D034072	M1	0.00	<0.005	0.001
59.00	60.50	D034080	D034079	1.50	<0.005	0.001
72.50	72.50	D034090	K	0.00	1.135	1.135
86.00	87.50	D034100	D034099	1.50	<0.005	0.001
99.50	99.50	D034110	L	0.00	2.220	2.220
101.00	101.00	D034112	M1	0.00	<0.005	0.001
111.50	113.00	D034120	D034119	1.50	0.011	0.011
125.00	125.00	D034130	M	0.00	3.070	3.070
138.50	140.00	D034140	D034139	1.50	<0.005	0.001
152.00	152.00	D034150	J	0.00	0.721	0.721
153.50	153.50	D034152	M1	0.00	<0.005	0.001
164.00	165.50	D034160	D034159	1.50	<0.005	0.001
177.50	177.50	D034170	K	0.00	1.040	1.040

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-195</b>	Titre minier :	Section :	631300
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley et freres	Lot :		
Décrit par : Sylvain SAVADOGO	Du : 2010-04-28	Date de description :	2010-06-29
	Au : 2010-04-29		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 122.00 m

UTM

Est	631 300.0
Nord	5 374 550.0
Élévation	282.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	41.30°	-60.60°	Oui
Reflex	8.00	42.20°	-60.80°	Oui
Reflex	11.00	346.60°	-60.20°	Oui
Reflex	14.00	346.30°	-59.30°	Oui
Reflex	17.00	343.00°	-58.90°	Oui
Reflex	20.00	340.70°	-58.80°	Oui
Reflex	23.00	353.60°	-59.10°	Oui
Reflex	26.00	355.00°	-58.60°	Oui
Reflex	29.00	341.10°	-57.80°	Oui
Reflex	32.00	348.10°	-56.70°	Oui
Reflex	35.00	344.50°	-56.20°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	339.60°	-56.30°	Oui
Reflex	41.00	7.50°	-56.30°	Non
Reflex	44.00	8.60°	-56.30°	Non
Reflex	47.00	8.70°	-56.20°	Non
Reflex	50.00	8.80°	-56.30°	Non
Reflex	53.00	8.40°	-56.30°	Non
Reflex	56.00	8.90°	-56.30°	Non
Reflex	59.00	9.20°	-56.30°	Non
Reflex	62.00	9.00°	-56.30°	Non
Reflex	65.00	9.10°	-56.20°	Non
Reflex	68.00	9.20°	-56.30°	Non
Reflex	71.00	9.10°	-56.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	35.30	MT <b>Mort-terrain</b> MT						
35.30	122.00	BA; AMY <b>Basalte; Amygdalaire</b> Basalte contenant quelques amygdules; partiellement plus ou moins carbonaté; pyrite disséminé dans la matrice; contenant quelques vQz centimétriques; BA amygdalaire à partir de 98m; avec des amygdules de Qz-CC, des amygdules de CC et de FP-CC;	35.30	37.00	D034779	1.70	<0.005	0.001
			37.00	38.00	D034781	1.00	<0.005	0.001
			38.00	39.50	D034782	1.50	<0.005	0.001
			39.50	41.00	D034783	1.50	<0.005	0.001
			41.00	42.50	D034784	1.50	<0.005	0.001
35.30	39.50	CB03 <b>Carbonaté 3</b> plus ou moins carbonaté						
42.50	122.00	CB05 <b>Carbonaté 5</b> plus ou moins et modérément carbonaté;	42.50	44.00	D034785	1.50	<0.005	0.001
			44.00	45.50	D034786	1.50	<0.005	0.001
			45.50	47.00	D034787	1.50	<0.005	0.001
			47.00	48.50	D034788	1.50	<0.005	0.001
			48.50	50.00	D034789	1.50	0.006	0.006
			50.00	51.50	D034791	1.50	<0.005	0.001
			51.50	53.00	D034793	1.50	<0.005	0.001
			53.00	54.50	D034794	1.50	<0.005	0.001
			54.50	56.00	D034795	1.50	<0.005	0.001
			56.00	57.50	D034796	1.50	<0.005	0.001
			57.50	58.80	D034797	1.30	<0.005	0.001
			59.00	60.50	D034798	1.50	<0.005	0.001
			60.50	62.00	D034799	1.50	<0.005	0.001
			62.00	63.50	D034801	1.50	<0.005	0.001
			63.50	65.00	D034802	1.50	<0.005	0.001
			65.00	66.50	D034803	1.50	<0.005	0.001
			66.50	68.00	D034804	1.50	0.005	0.005
			68.00	69.50	D034805	1.50	<0.005	0.001
			69.50	71.00	D034806	1.50	<0.005	0.001
			71.00	72.50	D034807	1.50	<0.005	0.001
			72.50	74.00	D034808	1.50	<0.005	0.001
			74.00	75.50	D034809	1.50	<0.005	0.001
			75.50	77.00	D034811	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
89.00      98.00      Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée entre 0,2% et 0,5% dans la matrice;	77.00	78.00	D034812	1.00	<0.005		0.001
	78.00	79.00	D034813	1.00	<0.005		0.001
	79.50	81.00	D034814	1.50	<0.005		0.001
	81.00	82.00	D034815	1.00	<0.005		0.001
	82.00	83.00	D034816	1.00	<0.005		0.001
	83.00	84.50	D034817	1.50	<0.005		0.001
	84.50	86.00	D034818	1.50	<0.005		0.001
	86.00	87.50	D034819	1.50	<0.005		0.001
	87.50	89.00	D034821	1.50	<0.005		0.001
	89.00	90.50	D034822	1.50	<0.005		0.001
	90.50	92.00	D034823	1.50	<0.005		0.001
	92.00	93.50	D034824	1.50	<0.005		0.001
	93.50	95.00	D034825	1.50	<0.005		0.001
	95.00	96.50	D034826	1.50	<0.005		0.001
	96.50	98.00	D034827	1.50	<0.005		0.001
	98.00	99.50	D034828	1.50	<0.005		0.001
	99.50	101.00	D034829	1.50	<0.005		0.001
	101.00	102.50	D034831	1.50	<0.005		0.001
	102.50	104.00	D034833	1.50	<0.005		0.001
	104.00	105.50	D034834	1.50	<0.005		0.001
	105.50	107.00	D034835	1.50	<0.005		0.001
	107.00	108.50	D034836	1.50	<0.005		0.001
	108.50	110.00	D034837	1.50	<0.005		0.001
110.00	111.50	D034838	1.50	<0.005		0.001	
111.50	113.00	D034839	1.50	<0.005		0.001	
113.00	114.50	D034841	1.50	<0.005		0.001	
114.50	116.00	D034842	1.50	<0.005		0.001	
116.00	117.50	D034843	1.50	<0.005		0.001	
117.50	119.00	D034844	1.50	<0.005		0.001	
119.00	120.50	D034845	1.50	<0.005		0.001	
120.50	122.00	D034846	1.50	<0.005		0.001	

# Corporation Minière Osisko Div. Exploration

122.00

Fin du sondage

Nombre d'échantillons : 59

Nombre d'échantillons QAQC : 9

Longueur totale échantillonnée : 86.00



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
35.30	37.00	D034780	D034779	1.70	<0.005	0.001
48.50	48.50	D034790	J	0.00	0.751	0.751
50.00	50.00	D034792	M1	0.00	<0.005	0.001
60.50	62.00	D034800	D034799	1.50	<0.005	0.001
74.00	74.00	D034810	K	0.00	1.105	1.105
86.00	87.50	D034820	D034819	1.50	<0.005	0.001
99.50	99.50	D034830	L	0.00	2.050	2.050
101.00	101.00	D034832	M1	0.00	<0.005	0.001
111.50	113.00	D034840	D034839	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	56.00	MT <b>Mort-terrain</b> No recovery et casing.							
56.00	57.90	GA <b>Gabbro</b> Gabbro moucheté. Gros pyroxènes. Réseau de veine/veinule/cheveux. Pas de minéralisation en pyrite et beaucoup de boxworks. Très altéré. Non carbonaté ni magnétique. Chloritisé.							
56.00	69.30	FRC <b>Fracturé</b> Très fracturé.	56.00	57.00	D031396	1.00	<0.005		0.001
57.00	60.20	SR <b>Séricitique</b>	57.00	57.90	D031397	0.90	<0.005		0.001
57.90	59.00	NR <b>Carotte perdue</b> Core Loss.							
59.00	60.20	GA <b>Gabbro</b> Gabbro moucheté. Gros pyroxènes. Réseau de veine/veinule/cheveux. Pas de minéralisation en pyrite et beaucoup de boxworks. Très altéré. Non carbonaté ni magnétique. Chloritisé.	59.00	60.20	D031398	1.20	<0.005		0.001
60.20	62.00	NR <b>Carotte perdue</b> Core loss.							
62.00	70.90	GA <b>Gabbro</b> Gabbro moucheté. Gros pyroxènes. Réseau de veine/veinule/cheveux. Pas de minéralisation en pyrite et beaucoup de boxworks. Très altéré. Non carbonaté ni magnétique. Chloritisé.	62.00	63.50	D031399	1.50	<0.005		0.001
			63.50	65.00	D031400	1.50	<0.005		0.001
			65.00	66.50	D031401	1.50	<0.005		0.001
			66.50	68.00	D031402	1.50	<0.005		0.001
			68.00	69.50	D031404	1.50	<0.005		0.001
			69.50	70.90	D031405	1.40	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
70.90	71.00	NR <b>Carotte perdue</b> No recovery.							
71.00	79.10	GA <b>Gabbro</b> Gabbro moucheté. Gros pyroxènes. Réseau de veine/veinule/cheveux. Pas de minéralisation en pyrite. Non carbonaté ni magnétique. Chloritisé.	71.00	72.50	D031406	1.50	<0.005		0.001
			72.50	74.00	D031407	1.50	<0.005		0.001
			74.00	75.50	D031408	1.50	0.011		0.011
			75.50	77.00	D031409	1.50	0.022		0.022
76.80	81.70	FRC <b>Fracturé</b> Très fracturé.							
77.00	79.10	SR <b>Séricitique</b>	77.00	78.00	D031411	1.00	<0.005		0.001
			78.00	79.10	D031412	1.10	<0.005		0.001
79.10	80.00	NR <b>Carotte perdue</b> No recovery.							
80.00	91.60	GA <b>Gabbro</b> Gabbro moucheté. Gros pyroxènes. Réseau de veine/veinule/cheveux. Pas de minéralisation en pyrite. Non carbonaté ni magnétique. Chloritisé.	80.00	81.50	D031414	1.50	0.005		0.005
			81.50	83.00	D031415	1.50	<0.005		0.001
			83.00	84.50	D031416	1.50	<0.005		0.001
			84.50	86.00	D031417	1.50	<0.005		0.001
			86.00	87.50	D031418	1.50	<0.005		0.001
			87.50	89.00	D031419	1.50	<0.005		0.001
			89.00	90.00	D031420	1.00	<0.005		0.001
90.00	91.60	SR <b>Séricitique</b>							
90.00	91.60	FRC <b>Fracturé</b> Très fracturé.	90.00	91.60	D031421	1.60	<0.005		0.001
91.60	92.00	NR <b>Carotte perdue</b> No recovery.							

# Corporation Minière Osisko Div. Exploration

92.00

Fin du sondage

Nombre d'échantillons : 23

Nombre d'échantillons QAQC : 3

Longueur totale échantillonnée : 31.70

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
66.50	68.00	D031403	D031402	1.50	<0.005	0.001
75.50	75.50	D031410	M1	0.00	<0.005	0.001
78.00	78.00	D031413	J	0.00	0.795	0.795

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-197**

Titre minier :

Section :                      631200

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Gilles.KAMTA

Lot :

Du :                      2010-04-30

Date de description :

Au :                      2010-05-01

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -68.00°  
 Longueur :                      225.00 m

Est	631 200.3
Nord	5 374 520.4
Élévation	283.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	350.10°	-68.50°	Non
Reflex	9.00	337.30°	-68.70°	Oui
Reflex	12.00	348.10°	-67.80°	Non
Reflex	15.00	349.60°	-67.40°	Non
Reflex	18.00	349.30°	-67.10°	Non
Reflex	21.00	115.60°	-67.10°	Oui
Reflex	24.00	1.20°	-67.10°	Non
Reflex	27.00	1.70°	-67.20°	Non
Reflex	30.00	1.60°	-67.00°	Non
Reflex	33.00	1.60°	-67.00°	Non
Reflex	36.00	1.50°	-66.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	3.20°	-66.80°	Oui
Reflex	42.00	2.70°	-66.80°	Non
Reflex	45.00	2.00°	-66.80°	Non
Reflex	48.00	1.80°	-66.70°	Non
Reflex	51.00	1.60°	-66.70°	Non
Reflex	54.00	1.50°	-66.70°	Non
Reflex	57.00	1.00°	-66.60°	Non
Reflex	60.00	1.00°	-66.60°	Non
Reflex	63.00	1.00°	-66.60°	Non
Reflex	66.00	0.80°	-66.60°	Non
Reflex	69.00	1.00°	-66.50°	Non
Reflex	72.00	0.90°	-66.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	19.60	MT <b>Mort-terrain</b>						
19.60	22.00	BA; MAS; AMY	19.60	20.80	D027028	1.20	<0.005	0.001
		<b>Basalte; Roche massive; Amygdalaire</b> massive altération en calcite et chlorite, veines veinules de carbonâtes	20.80	22.00	D027029	1.20	<0.005	0.001
22.00	23.00	NR <b>Carotte perdue</b> fragments cm sub arrondi						
23.00	75.60	BA; AMY <b>Basalte; Amygdalaire</b> altération en calcite et chlorite, amydules mm carbonaté, PY irrég diss	23.00	24.50	D027030	1.50	<0.005	0.001
			24.50	26.00	D027031	1.50	<0.005	0.001
			26.00	27.50	D027032	1.50	0.005	0.005
			27.50	29.00	D027033	1.50	0.011	0.011
			29.00	30.50	D027034	1.50	0.005	0.005
			30.50	32.00	D027035	1.50	<0.005	0.001
			32.00	33.50	D027036	1.50	<0.005	0.001
			33.50	35.00	D027038	1.50	0.005	0.005
			35.00	36.50	D027039	1.50	<0.005	0.001
			36.50	38.00	D027040	1.50	0.005	0.005
			38.00	39.50	D027041	1.50	<0.005	0.001
			39.50	41.00	D027042	1.50	<0.005	0.001
			41.00	42.50	D027043	1.50	<0.005	0.001
			42.50	44.00	D027044	1.50	<0.005	0.001
			44.00	45.50	D027045	1.50	0.006	0.006
			45.50	47.00	D027046	1.50	0.007	0.007
			47.00	48.50	D027048	1.50	<0.005	0.001
			48.50	50.00	D027049	1.50	0.005	0.005
			50.00	51.50	D027050	1.50	0.005	0.005
			51.50	53.00	D027051	1.50	<0.005	0.001
			53.00	54.50	D027052	1.50	0.005	0.005
			54.50	56.00	D027053	1.50	<0.005	0.001
			56.00	57.50	D027054	1.50	<0.005	0.001
			57.50	59.00	D027055	1.50	0.005	0.005
			59.00	60.50	D027056	1.50	0.005	0.005
			60.50	62.00	D027058	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			62.00	63.50	D027059	1.50	<0.005		0.001	
			63.50	65.00	D027060	1.50	<0.005		0.001	
			65.00	66.50	D027061	1.50	<0.005		0.001	
			66.50	68.00	D027062	1.50	<0.005		0.001	
			68.00	69.50	D027063	1.50	<0.005		0.001	
			69.50	71.00	D027065	1.50	<0.005		0.001	
			71.00	72.50	D027066	1.50	<0.005		0.001	
			72.50	74.00	D027068	1.50	<0.005		0.001	
			74.00	75.60	D027069	1.60	<0.005		0.001	
75.60	78.10	SY; POR; FIN	75.60	77.00	D027070	1.40	<0.005		0.001	
		<b>Syénite 50°; Porphyrique; Grains fins</b>	77.00	78.10	D027071	1.10	<0.005		0.001	
		altération en silice avec phénocristaux de FP automorphe ou sub arrondi blanchâtre, +++calcite, CL++								
78.10	80.80	BA; VES	78.10	79.40	D027072	1.30	<0.005		0.001	
		<b>Basalte 30°; Vésiculaire</b>								
		altération en calcite et chlorite, fragments mêlés, PY automorphe et fine diss								
	79.40	80.00	FRC	79.40	80.80	D027073	1.40	<0.005		0.001
			<b>Fracturé</b>							
80.80	85.20	SY; POR	80.80	82.50	D027074	1.70	0.005		0.005	
		<b>Syénite 30°; Porphyrique</b>	82.50	84.00	D027075	1.50	<0.005		0.001	
		induré, altération en s séricite et chlorite, phénocristaux de FP sub automorphe, CL+++; SR+, PY fine								
	83.30	86.50	FRC	84.00	85.20	D027076	1.20	<0.005		0.001
			<b>Fracturé</b>							
85.20	89.00	BA; VES	85.20	86.50	D027078	1.30	<0.005		0.001	
		<b>Basalte 30°; Vésiculaire</b>								
		altération en chlorite et calcite, vacuoles mm, carbonâtes								
	86.50	89.00	FRC	86.50	88.00	D027079	1.50	<0.005		0.001
			<b>Fracturé</b>	88.00	89.00	D027080	1.00	<0.005		0.001
89.00	89.80	NR								
		<b>Carotte perdue</b>								
		boue verdâtre zone de faille probable								
89.80	118.90	BA; MAS	89.80	91.50	D027081	1.70	<0.005		0.001	
		<b>Basalte; Roche massive</b>	91.50	93.00	D027082	1.50	<0.005		0.001	
		localement vacuoles, altération en chlorite et calcite, carbonâtes	93.00	94.50	D027083	1.50	<0.005		0.001	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			94.50	96.00	D027084	1.50	<0.005		0.001
			96.00	97.50	D027085	1.50	0.008		0.008
			97.50	99.00	D027086	1.50	<0.005		0.001
			99.00	100.50	D027088	1.50	<0.005		0.001
			100.50	102.00	D027089	1.50	<0.005		0.001
			102.00	103.50	D027090	1.50	<0.005		0.001
			103.50	105.00	D027091	1.50	<0.005		0.001
			105.00	106.50	D027092	1.50	<0.005		0.001
			106.50	108.00	D027093	1.50	<0.005		0.001
			108.00	109.50	D027094	1.50	<0.005		0.001
			109.50	111.00	D027095	1.50	<0.005		0.001
			111.00	112.50	D027096	1.50	<0.005		0.001
			112.50	114.00	D027098	1.50	0.005		0.005
			114.00	115.50	D027099	1.50	<0.005		0.001
			115.50	117.00	D027100	1.50	<0.005		0.001
			117.00	118.00	D027101	1.00	<0.005		0.001
			118.00	118.90	D027102	0.90	<0.005		0.001
118.90	122.00	GR; LAM	118.90	120.00	D027103	1.10	0.005		0.005
		<b>Grès 30°; Laminations parallèles</b>	120.00	121.00	D027105	1.00	0.024		0.024
		localement massive, laminations et litage 30° ac ou sub // ac, SR++, CL++, BO++, graphite, PY fine diss	121.00	122.00	D027106	1.00	0.015		0.015
122.00	124.60	SY; POR	122.00	123.00	D027108	1.00	<0.005		0.001
		<b>Syénite 40°; Porphyrique</b>	123.00	124.60	D027109	1.60	<0.005		0.001
		grains fin, phénocristaux de FP automorphe 0.2-0.7 cm CL+, BO++, SR+, PY fine diss	124.60	126.00	D027110	1.40	<0.005		0.001
124.60	135.00	GR; FIN	126.00	127.50	D027111	1.50	0.006		0.006
		<b>Grès 30°; Grains fins</b>	127.50	128.60	D027112	1.10	0.008		0.008
		grains fin à mudstone, litage 30° ac, localement légère altération en silice, chloritisation, biotisation, vCC 40-60° ac,	128.60	130.00	D027113	1.40	<0.005		0.001
128.80	128.83	FAI	130.00	131.50	D027114	1.50	<0.005		0.001
		<b>Faille 40°</b>	131.50	133.00	D027115	1.50	0.008		0.008
		boue verdâtre	133.00	134.00	D027116	1.00	0.009		0.009
134.00	135.00	FRC	134.00	135.00	D027118	1.00	0.008		0.008
		<b>Fracturé</b>							
		fragments cm, zones milonitisé, boue blanchâtre et verdâtre							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
135.00	198.00	BA; MAS <b>Basalte 50°; Roche massive</b> massive, passage à amygdules yeux de QZ mm, altération en calcite et chlorite, silicification	135.00	136.50	D027119	1.50	<0.005		0.001
			136.50	138.00	D027120	1.50	<0.005		0.001
			138.00	139.50	D027121	1.50	<0.005		0.001
			139.50	141.00	D027122	1.50	<0.005		0.001
			141.00	142.50	D027123	1.50	<0.005		0.001
			142.50	144.00	D027124	1.50	<0.005		0.001
			144.00	145.50	D027125	1.50	0.005		0.005
			145.50	147.00	D027126	1.50	<0.005		0.001
			147.00	148.50	D027128	1.50	<0.005		0.001
			148.50	150.00	D027129	1.50	<0.005		0.001
			150.00	151.50	D027130	1.50	<0.005		0.001
			151.50	153.00	D027131	1.50	<0.005		0.001
			153.00	154.50	D027132	1.50	<0.005		0.001
			154.50	156.00	D027133	1.50	<0.005		0.001
			156.00	157.50	D027134	1.50	0.005		0.005
			157.50	159.00	D027135	1.50	0.018		0.018
			159.00	160.50	D027136	1.50	<0.005		0.001
			160.50	162.00	D027138	1.50	<0.005		0.001
			162.00	163.50	D027139	1.50	<0.005		0.001
			163.50	165.00	D027140	1.50	<0.005		0.001
165.00	166.50	D027141	1.50	<0.005		0.001			
166.50	168.00	D027142	1.50	<0.005		0.001			
168.00	169.50	D027143	1.50	<0.005		0.001			
169.50	171.00	D027145	1.50	<0.005		0.001			
171.00	172.50	D027146	1.50	<0.005		0.001			
172.50	174.00	D027148	1.50	0.006		0.006			
173.80	174.00	FAI <b>Faille 40°</b> fracturé avec boue Verdâtre et fragments mm- cm	174.00	175.70	D027149	1.70	0.006		0.006
175.30	175.50	FAI <b>Faille 50°</b> zone fragmenté, boue verdâtre	175.70	177.20	D027150	1.50	<0.005		0.001
176.00	176.60	FRC <b>Fracturé</b> passage millonotisé bou blanchâtre et verdâtre	177.20	178.50	D027151	1.30	<0.005		0.001
			178.50	180.00	D027152	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			180.00	181.50	D027153	1.50	<0.005		0.001
			181.50	183.00	D027154	1.50	<0.005		0.001
			183.00	184.50	D027155	1.50	<0.005		0.001
			184.50	186.00	D027156	1.50	<0.005		0.001
			186.00	187.50	D027158	1.50	<0.005		0.001
			187.50	189.00	D027159	1.50	<0.005		0.001
			189.00	190.50	D027160	1.50	<0.005		0.001
			190.50	192.00	D027161	1.50	<0.005		0.001
			192.00	193.50	D027162	1.50	<0.005		0.001
			193.50	195.00	D027163	1.50	<0.005		0.001
			195.00	196.50	D027164	1.50	<0.005		0.001
			196.50	198.00	D027165	1.50	<0.005		0.001
198.00	200.00	GR; FIN	198.00	199.00	D027166	1.00	0.007		0.007
		<b>Grès 30°; Grains fins</b>	199.00	200.00	D027168	1.00	0.018		0.018
		massive, grenue à grains fin, localement massive, litage et laminations 10-40° ac, graphite, chlorite, séricite, biotite, localement altéré en calcite							
200.00	202.00	NR							
		<b>Carotte perdue</b>							
201.00	209.00	FRC	201.00	202.50	D027169	1.50	0.034		0.034
		<b>Fracturé</b>							
		fragments mêlés cm							
202.00	209.00	GR; FIN	202.50	204.00	D027170	1.50	0.012		0.012
		<b>Grès; Grains fins</b>	204.00	205.50	D027171	1.50	0.008		0.008
		grenue, fragments cm, zones milonitisé, altération en calcite, biotite, chlorite et séricite, litage et laminations, PY en amas et fine diss	205.50	207.00	D027172	1.50	0.013		0.013
			207.00	208.00	D027173	1.00	0.007		0.007
			208.00	209.00	D027174	1.00	0.008		0.008
209.00	217.00	BA; VES							
		<b>Basalte 30°; Vésiculaire</b>							
		localement massive, vacuoles, altération en calcite, CL+++ , BO+, calcite							
209.00	217.00	FRC	209.00	210.50	D027175	1.50	<0.005		0.001
		<b>Fracturé</b>	210.50	212.00	D027176	1.50	0.005		0.005
		zone de faille avec fragments mm-cm, localement boue verdâtre	212.00	213.50	D027178	1.50	<0.005		0.001
			213.50	215.00	D027179	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			215.00	216.00	D027180	1.00	<0.005		0.001	
			216.00	217.00	D027181	1.00	0.005		0.005	
217.00	217.50	NR <b>Carotte perdue</b>								
217.50	225.00	BA; MAS <b>Basalte; Roche massive</b> massive, altération en calcite, chlorite, carbonâtes	217.50	219.00	D027182	1.50	<0.005		0.001	
			219.00	220.50	D027183	1.50	<0.005		0.001	
			220.50	222.00	D027185	1.50	<0.005		0.001	
			222.00	223.50	D027186	1.50	<0.005		0.001	
			223.50	225.00	D027188	1.50	0.005		0.005	
225.00	Fin du sondage Nombre d'échantillons : 141 Nombre d'échantillons QAQC : 20 Longueur totale échantillonnée : 202.10									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
32.00	33.50	D027037	D027036	1.50	0.005	0.005
45.50	45.50	D027047	J	0.00	0.764	0.764
59.00	60.50	D027057	D027056	1.50	<0.005	0.001
68.00	68.00	D027064	M1	0.00	<0.005	0.001
71.00	71.00	D027067	K	0.00	1.025	1.025
84.00	85.20	D027077	D027076	1.20	<0.005	0.001
97.50	97.50	D027087	L	0.00	2.030	2.030
111.00	112.50	D027097	D027096	1.50	<0.005	0.001
118.90	118.90	D027104	M1	0.00	<0.005	0.001
121.00	121.00	D027107	M	0.00	2.950	2.950
133.00	134.00	D027117	D027116	1.00	0.008	0.008
145.50	145.50	D027127	J	0.00	0.795	0.795
159.00	160.50	D027137	D027136	1.50	<0.005	0.001
168.00	168.00	D027144	M1	0.00	<0.005	0.001
171.00	171.00	D027147	K	0.00	1.005	1.005
184.50	186.00	D027157	D027156	1.50	<0.005	0.001
198.00	198.00	D027167	L	0.00	2.060	2.060
210.50	212.00	D027177	D027176	1.50	<0.005	0.001
219.00	219.00	D027184	M1	0.00	<0.005	0.001
222.00	222.00	D027187	M	0.00	2.640	2.640

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-198**

Titre minier :

Section :                      630800

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Johan Bergé

Lot :

Du :                              2010-05-01

Date de description :

Au :                              2010-05-06

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      476.00 m

Est	630 799.6
Nord	5 374 255.5
Élévation	303.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	5.80°	-60.10°	Oui
Reflex	8.00	5.70°	-60.10°	Oui
Reflex	11.00	350.00°	-60.30°	Oui
Reflex	14.00	357.40°	-60.20°	Oui
Reflex	17.00	0.10°	-60.00°	Non
Reflex	20.00	0.40°	-60.20°	Non
Reflex	23.00	0.40°	-60.20°	Non
Reflex	26.00	0.70°	-60.20°	Non
Reflex	29.00	0.90°	-60.20°	Non
Reflex	32.00	1.00°	-60.30°	Non
Reflex	35.00	1.10°	-60.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.20°	-60.20°	Non
Reflex	41.00	1.20°	-60.20°	Non
Reflex	44.00	1.20°	-60.00°	Non
Reflex	47.00	0.80°	-59.70°	Non
Reflex	50.00	0.50°	-59.60°	Non
Reflex	53.00	0.50°	-59.50°	Non
Reflex	56.00	0.40°	-59.60°	Non
Reflex	59.00	0.30°	-59.60°	Non
Reflex	62.00	0.30°	-59.50°	Non
Reflex	65.00	0.20°	-59.50°	Non
Reflex	68.00	0.10°	-59.30°	Non
Reflex	71.00	0.20°	-59.20°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	10.00	MT <b>Mort-terrain</b> Pas de carottes, blocs alloctones.							
10.00	43.20	SY <b>Syénite 60°</b> Syénite grossière, grain de quelques mm à 1cm. Les plus gros phénocristaux sont des feldspaths rectangulaires zonés peu altérés avec auréole d'altération. 30% de la roche. Le reste de la roche est très fortement hématisée, couleur rouge. Séricitisée. Le réseau de veine/veinule/cheveux est peu développé. La minéralisation en pyrite est en moyenne faible. Non magnétique.	10.00	11.50	D031766	1.50	0.124		0.124
			11.50	13.00	D031767	1.50	0.137		0.137
			13.00	14.50	D031768	1.50	0.473		0.473
			14.50	16.00	D031769	1.50	0.065		0.065
			16.00	17.50	D031771	1.50	0.159		0.159
			17.50	19.00	D031772	1.50	0.045		0.045
			19.00	20.50	D031774	1.50	0.073		0.073
			20.50	22.00	D031775	1.50	0.063		0.063
			22.00	23.50	D031776	1.50	0.077		0.077
			23.50	25.00	D031777	1.50	0.116		0.116
			25.00	26.50	D031778	1.50	0.146		0.146
			26.50	28.00	D031779	1.50	0.023		0.023
			28.00	29.50	D031780	1.50	0.110		0.110
			29.50	31.00	D031781	1.50	0.367		0.367
			31.00	32.50	D031782	1.50	0.014		0.014
			32.50	34.00	D031784	1.50	0.166		0.166
			34.00	35.50	D031785	1.50	0.268		0.268
10.00	41.60	HM <b>Hématisé</b> Syénite hématisé fortement. Couleur rouge.							
34.40	34.50	QZVN <b>Veine de Quartz massive 60°</b>	35.50	37.00	D031786	1.50	0.199		0.199
			37.00	38.50	D031787	1.50	0.082		0.082
			38.50	40.00	D031788	1.50	0.177		0.177
			40.00	41.60	D031789	1.60	0.034		0.034
41.60	43.20	SR <b>Séricitique</b> Syénite séricitisée. Porphyroblates toujours visibles.	41.60	43.20	D031790	1.60	0.037		0.037
43.20	125.30	DI <b>Diorite 70°</b> Diorite intrusive dans la syénite porphyrique. Cisaillement à 60'. Granulo fine.							



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
43.20	53.30	DI <b>Diorite</b> Diorite non carbonatée. Cisaillage très bien visible. 35°.						
43.20	125.30	CH <b>Chloriteux</b> Chloritisation poussée. Couleur verdâtre aux contacts avec les unités hématisées, vert-bleu sinon.	43.20	44.50	D031791	1.30	<0.005	0.001
			44.50	46.00	D031792	1.50	0.050	0.050
			46.00	47.50	D031794	1.50	<0.005	0.001
			47.50	49.00	D031795	1.50	<0.005	0.001
			49.00	50.50	D031796	1.50	<0.005	0.001
			50.50	52.00	D031797	1.50	0.007	0.007
			52.00	53.40	D031798	1.40	4.130	4.130
			53.40	55.00	D031799	1.60	0.345	0.345
			55.00	56.50	D031800	1.50	0.024	0.024
			56.50	58.00	D031801	1.50	0.006	0.006
			58.00	59.50	D031802	1.50	<0.005	0.001
			59.50	61.00	D031804	1.50	<0.005	0.001
			61.00	62.50	D031805	1.50	<0.005	0.001
			62.50	64.00	D031806	1.50	<0.005	0.001
63.70	64.30	FRC <b>Fracturé 10°</b> Fracture unique sub parallèle au trou de forage. Remplissage carbonaté.	64.00	65.50	D031807	1.50	<0.005	0.001
			65.50	67.00	D031808	1.50	<0.005	0.001
			67.00	68.50	D031809	1.50	<0.005	0.001
			68.50	70.00	D031811	1.50	<0.005	0.001
			70.00	71.50	D031812	1.50	<0.005	0.001
			71.50	73.00	D031814	1.50	<0.005	0.001
			73.00	74.50	D031815	1.50	<0.005	0.001
			74.50	76.00	D031816	1.50	<0.005	0.001
75.00	76.50	FRC <b>Fracturé 50°</b> Zone fracturée avec remplissage carbonaté.	76.00	77.50	D031817	1.50	<0.005	0.001
			77.50	79.00	D031818	1.50	0.005	0.005
			79.00	80.50	D031819	1.50	0.009	0.009
			80.50	82.00	D031820	1.50	0.333	0.333
81.40	81.60	FAI <b>Faille 40°</b> Faille remplie de morceaux fracturés de roche et de boue (fault)	82.00	83.00	D031821	1.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
82.90	83.00	gouge). Carbonatée. QZVN <b>Veine de Quartz massive</b>						
83.00	85.00	DI <b>Diorite</b> Diorite non carbonatée.	83.00	84.50	D031822	1.50	<0.005	0.001
			84.50	86.00	D031824	1.50	<0.005	0.001
85.00	85.10	QZVN <b>Veine de Quartz massive 40°</b>						
85.10	93.80	DI <b>Diorite</b> Diorite non carbonatée.	86.00	87.50	D031825	1.50	<0.005	0.001
			87.50	89.00	D031826	1.50	<0.005	0.001
			89.00	90.50	D031827	1.50	0.011	0.011
			90.50	92.20	D031828	1.70	<0.005	0.001
			92.20	93.80	D031829	1.60	<0.005	0.001
93.80	95.50	DI <b>Diorite</b> Diorite légèrement hématisée.	93.80	95.50	D031830	1.70	0.005	0.005
			95.50	97.00	D031831	1.50	<0.005	0.001
			97.00	98.50	D031832	1.50	<0.005	0.001
			98.50	100.00	D031834	1.50	0.005	0.005
			100.00	101.50	D031835	1.50	<0.005	0.001
			101.50	103.00	D031836	1.50	0.015	0.015
			103.00	104.50	D031837	1.50	<0.005	0.001
			104.50	106.00	D031838	1.50	<0.005	0.001
			106.00	107.50	D031839	1.50	<0.005	0.001
			107.50	109.00	D031840	1.50	<0.005	0.001
			109.00	110.50	D031841	1.50	<0.005	0.001
			110.50	112.00	D031842	1.50	0.005	0.005
			112.00	113.50	D031844	1.50	0.008	0.008
			113.50	115.00	D031845	1.50	<0.005	0.001
			115.00	116.00	D031846	1.00	0.280	0.280
			116.00	117.40	D031847	1.40	0.018	0.018
117.40	125.30	DI <b>Diorite</b> Diorite non carbonatée. Cisaillement bien visible à 40°.	117.40	119.00	D031848	1.60	2.290	2.290
			119.00	120.50	D031849	1.50	1.360	1.360
			120.50	122.00	D031851	1.50	0.718	0.718
122.00	122.70	CIS	122.00	123.60	D031852	1.60	1.755	1.755

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Cisaillement 20°</b> Zone bréchifiée, remplie par du quartz rosâtre, hématisé.	123.60	125.30	D031854	1.70	<0.005		0.001
125.30	476.00	<b>SY</b> <b>Syénite</b> Syénite grossière, grain de quelques mm à 1cm. Les plus gros phénocristaux sont des feldspaths peu altérés avec auréole d'altération. 20% de la roche. Le reste de la roche est très fortement hématisée, couleur rouge. Séricitisée. Le réseau de veine/veinule/cheveux est peu développé. La minéralisation en pyrite est en moyenne faible. Magnétique légèrement avec des zones non magnétiques métriques et des zones très magnétiques métriques. Quelques passages carbonatés c3.	125.30	127.00	D031855	1.70	<0.005		0.001
125.30	125.90	<b>SR</b> <b>Séricitique</b> Syénite porphyrique séricitisée.							
125.90	221.00	<b>HM</b> <b>Hématisé</b> Syénite hématisée.	127.00	128.50	D031856	1.50	<0.005		0.001
			128.50	130.00	D031857	1.50	<0.005		0.001
			130.00	131.50	D031858	1.50	<0.005		0.001
			131.50	133.00	D031859	1.50	<0.005		0.001
			133.00	134.50	D031860	1.50	<0.005		0.001
			134.50	136.00	D031861	1.50	<0.005		0.001
			136.00	137.50	D031862	1.50	<0.005		0.001
			137.50	139.00	D031864	1.50	<0.005		0.001
			139.00	140.50	D031865	1.50	0.101		0.101
			140.50	142.00	D031866	1.50	0.009		0.009
			142.00	143.50	D031867	1.50	0.007		0.007
			143.50	145.00	D031868	1.50	0.019		0.019
			145.00	146.50	D031869	1.50	0.012		0.012
146.50	149.80	<b>DI</b> <b>Diorite</b> Diorite carbonatée.	146.50	148.20	D031870	1.70	0.202		0.202
			148.20	149.80	D031871	1.60	0.168		0.168
			149.80	151.50	D031872	1.70	0.064		0.064
			151.50	153.00	D031874	1.50	0.005		0.005
			153.00	154.50	D031875	1.50	0.078		0.078
			154.50	156.00	D031876	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
163.60	171.50	DI <b>Diorite</b> Diorite carbonatée.	156.00	157.50	D031877	1.50	0.089		0.089
			157.50	159.00	D031878	1.50	<0.005		0.001
			159.00	160.50	D031879	1.50	0.025		0.025
			160.50	162.00	D031880	1.50	0.008		0.008
			162.00	163.60	D031881	1.60	<0.005		0.001
			163.60	165.00	D031882	1.40	<0.005		0.001
			165.00	166.00	D031884	1.00	0.101		0.101
			166.00	167.00	D031885	1.00	1.265		1.265
			167.00	168.50	D031886	1.50	0.070		0.070
			168.50	170.00	D031887	1.50	0.115		0.115
170.10	176.20	FRC <b>Fracturé 5°</b> Zone fracturée. Remplie par chlorite.	170.00	171.50	D031888	1.50	0.149		0.149
			171.50	173.00	D031889	1.50	0.005		0.005
			173.00	174.00	D031891	1.00	0.008		0.008
173.50	194.10	DI <b>Diorite</b> Diorite porphyrique de couleur rouge vin, très magnétique.	174.00	175.50	D031892	1.50	0.017		0.017
			175.50	177.00	D031894	1.50	0.197		0.197
			177.00	178.50	D031895	1.50	<0.005		0.001
			178.50	180.00	D031896	1.50	0.005		0.005
			180.00	181.50	D031897	1.50	<0.005		0.001
			181.50	183.00	D031898	1.50	<0.005		0.001
			183.00	184.00	D031899	1.00	0.009		0.009
			184.00	184.80	D031900	0.80	<0.005		0.001
			184.80	186.00	D031901	1.20	0.017		0.017
			186.00	186.90	D031902	0.90	0.005		0.005
			186.90	188.50	D031904	1.60	<0.005		0.001
			188.50	190.00	D031905	1.50	<0.005		0.001
			190.00	191.50	D031906	1.50	<0.005		0.001
			191.50	193.00	D031907	1.50	0.015		0.015
193.00	194.50	D031908	1.50	0.006		0.006			
194.50	196.00	D031909	1.50	<0.005		0.001			
196.00	197.50	D031910	1.50	<0.005		0.001			
197.50	199.00	D031911	1.50	<0.005		0.001			
199.00	200.50	D031912	1.50	0.024		0.024			
200.50	202.00	D031914	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
202.60	202.70	QZVN <b>Veine de Quartz massive 40°</b> Veine de quartz carbonate (dont ankérite oxydé de couleur jaunâtre). Peu minéralisé.	202.00	203.50	D031915	1.50	0.180		0.180
			203.50	205.00	D031916	1.50	<0.005		0.001
			205.00	206.50	D031917	1.50	<0.005		0.001
206.50	207.10	QZVN <b>Veine de Quartz massive 5°</b> Veine de quartz carbonate ankérisée avec présence de molybdène et de pyrite par endroit.	206.50	208.00	D031918	1.50	<0.005		0.001
			208.00	209.50	D031919	1.50	<0.005		0.001
			209.50	211.00	D031920	1.50	<0.005		0.001
			211.00	212.50	D031921	1.50	<0.005		0.001
			212.50	214.00	D031922	1.50	0.006		0.006
			214.00	215.50	D031924	1.50	0.006		0.006
			215.50	217.00	D031925	1.50	0.065		0.065
			217.00	218.50	D031926	1.50	<0.005		0.001
			218.50	220.00	D031927	1.50	0.205		0.205
			220.00	221.50	D031928	1.50	<0.005		0.001
221.00	238.00	HM; CH <b>Hématisé; Chloriteux</b> Alternance métrique de zone chloritisée et hématisée.	221.50	223.00	D031929	1.50	0.009		0.009
			223.00	224.50	D031931	1.50	<0.005		0.001
			224.50	226.00	D031932	1.50	0.021		0.021
			226.00	227.50	D031934	1.50	0.113		0.113
			227.50	229.00	D031935	1.50	0.192		0.192
			229.00	230.50	D031936	1.50	0.016		0.016
			230.50	232.00	D031937	1.50	0.008		0.008
			232.00	233.50	D031938	1.50	0.620		0.620
			233.50	235.00	D031939	1.50	0.195		0.195
			235.00	236.50	D031940	1.50	0.063		0.063
238.00	239.50	CH <b>Chloriteux</b>	236.50	238.00	D031941	1.50	0.014		0.014
			238.00	239.50	D031942	1.50	0.224		0.224
239.50	246.90	HM <b>Hématisé</b>	239.50	241.00	D031944	1.50	0.018		0.018
240.60	243.70	FRC <b>Fracturé 45°</b> Zone fracturée.	241.00	242.50	D031945	1.50	0.096		0.096
			242.50	244.00	D031946	1.50	0.052		0.052
			244.00	245.50	D031947	1.50	0.014		0.014

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
246.90	260.10	CH; HM <b>Chloriteux; Hématisé</b> Surtout chloritisé, et hématisé par endroit.	245.50	247.00	D031948	1.50	0.011		0.011
			247.00	248.50	D031949	1.50	0.044		0.044
			248.50	250.00	D031950	1.50	0.014		0.014
			250.00	251.50	D031951	1.50	0.076		0.076
			251.50	253.20	D031952	1.70	0.095		0.095
251.60	253.80	QZVN <b>Veine de Quartz massive</b> Veine de quartz carbonate 10' parcourrant la syénite accompagnée de multiple veines de quartz ondulantes. Coloration rose (hématisation) accompagnée d'ankérite (jaune orange) et de chlorite (vert).	253.20	254.50	D031954	1.30	0.059		0.059
			254.50	256.00	D031955	1.50	0.026		0.026
			256.00	257.50	D031956	1.50	0.005		0.005
			257.50	259.20	D031957	1.70	0.014		0.014
			259.20	260.80	D031958	1.60	0.075		0.075
260.10	315.50	HM <b>Hématisé</b> Hématisé, avec de rares passages décimétriques chloritisés.	260.80	262.00	D031959	1.20	0.050		0.050
			262.00	263.50	D031960	1.50	0.905		0.905
			263.50	265.00	D031961	1.50	0.007		0.007
			265.00	266.50	D031962	1.50	0.005		0.005
			266.50	268.00	D031964	1.50	<0.005		0.001
			268.00	269.50	D031965	1.50	<0.005		0.001
			269.50	271.00	D031966	1.50	<0.005		0.001
			271.00	272.50	D031967	1.50	<0.005		0.001
			272.50	274.00	D031968	1.50	0.050		0.050
			274.00	275.50	D031969	1.50	0.007		0.007
			275.50	277.00	D031971	1.50	0.011		0.011
			277.00	278.50	D031972	1.50	0.019		0.019
			278.50	280.00	D031974	1.50	0.021		0.021
			280.00	281.50	D031975	1.50	0.005		0.005
			281.50	283.00	D031976	1.50	0.007		0.007
283.00	284.50	D031977	1.50	0.013		0.013			
284.50	286.00	D031978	1.50	0.010		0.010			
286.00	287.50	D031979	1.50	0.177		0.177			
286.90	294.00	SY; POR <b>Syénite; Porphyrique</b> Grande proportion de feldspath porphyritique. Porphyre trachytique.	287.50	289.00	D031980	1.50	<0.005		0.001
			289.00	290.50	D031981	1.50	0.037		0.037
			290.50	292.00	D031982	1.50	<0.005		0.001
			292.00	293.50	D031984	1.50	0.005		0.005
			293.50	295.00	D031985	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
296.40	296.70	SY <b>Syénite</b> Syénite bréchifiée. Claste cm de syénite hématisée dans une matrice très carbonatée.	295.00	296.30	D031986	1.30	<0.005		0.001
			296.30	298.00	D031987	1.70	<0.005		0.001
			298.00	299.50	D031988	1.50	<0.005		0.001
			299.50	301.00	D031989	1.50	<0.005		0.001
300.00	307.00	SY; POR <b>Syénite; Porphyrique</b> Porphyre trachytitique avec une grande proportion de feldspath (>50%).	301.00	302.50	D031990	1.50	<0.005		0.001
			302.50	304.00	D031991	1.50	0.005		0.005
			304.00	305.50	D031992	1.50	<0.005		0.001
			305.50	307.00	D031994	1.50	0.005		0.005
			307.00	308.30	D031995	1.30	<0.005		0.001
			308.30	309.30	D031996	1.00	<0.005		0.001
			309.30	311.00	D031997	1.70	0.073		0.073
			311.00	312.50	D031998	1.50	0.044		0.044
			312.50	314.00	D031999	1.50	<0.005		0.001
315.50	321.00	CH <b>Chloriteux</b> La syénite chloriteuse est de granulo plus fine, plus riche en pyrite.	314.00	315.50	D032000	1.50	0.081		0.081
			315.50	317.00	D039001	1.50	0.212		0.212
			317.00	318.50	D039002	1.50	0.150		0.150
			318.50	320.00	D039004	1.50	0.016		0.016
			320.00	321.50	D039005	1.50	0.021		0.021
321.00	365.80	HM <b>Hématisé</b>	321.50	323.00	D039006	1.50	0.007		0.007
			323.00	324.50	D039007	1.50	0.011		0.011
			324.50	326.00	D039008	1.50	0.009		0.009
325.90	327.40	SY; POR <b>Syénite; Porphyrique</b> Porphyroblates de taille supérieure à la normale (moyenne cm).  Porphyre trachytitique, porphyroblates isométriques et parallèle à l'axe du trou.	326.00	327.50	D039009	1.50	0.015		0.015
			327.50	329.00	D039011	1.50	0.019		0.019
			329.00	330.50	D039012	1.50	0.157		0.157
			330.50	332.00	D039014	1.50	0.007		0.007
			332.00	333.50	D039015	1.50	0.006		0.006
			333.50	335.00	D039016	1.50	<0.005		0.001
			335.00	336.50	D039017	1.50	0.019		0.019
			336.50	338.00	D039018	1.50	0.797		0.797
			338.00	339.50	D039019	1.50	0.009		0.009
			339.50	341.00	D039020	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			341.00	342.30	D039021	1.30		0.005		0.005
			342.30	344.00	D039022	1.70		0.008		0.008
			344.00	345.50	D039024	1.50		<0.005		0.001
			345.50	347.00	D039025	1.50		0.958		0.958
			347.00	348.50	D039026	1.50		0.017		0.017
			348.50	350.00	D039027	1.50		0.017		0.017
			350.00	351.50	D039028	1.50		0.009		0.009
			351.50	353.00	D039029	1.50		0.008		0.008
			353.00	354.00	D039030	1.00		0.005		0.005
			354.00	355.00	D039031	1.00		0.005		0.005
			355.00	356.50	D039032	1.50		0.031		0.031
			356.50	358.00	D039034	1.50		0.041		0.041
			358.00	359.50	D039035	1.50		<0.005		0.001
			359.50	361.00	D039036	1.50		<0.005		0.001
			361.00	362.50	D039037	1.50		0.044		0.044
			362.50	364.10	D039038	1.60		0.102		0.102
			364.10	365.80	D039039	1.70		0.216		0.216
365.80	367.20	CH <b>Chloriteux</b> Passage progressif HW hem->chl et FW chl->ser.	365.80	367.20	D039040	1.40		0.127		0.127
367.20	369.80	SR <b>Séricitique</b> Passage progressif FW ser->hem.	367.20	368.50	D039041	1.30		0.045		0.045
			368.50	370.00	D039042	1.50		0.202		0.202
369.80	393.60	HM <b>Hématisé</b> Généralement hématisé avec passage décimétriques chloritisés ou séricitisés.	370.00	371.50	D039044	1.50		1.105		1.105
			371.50	373.00	D039045	1.50		0.230		0.230
			373.00	374.50	D039046	1.50		0.507		0.507
			374.50	376.00	D039047	1.50		0.440		0.440
			376.00	377.50	D039048	1.50		0.010		0.010
			377.50	379.00	D039049	1.50		0.006		0.006
			379.00	380.50	D039051	1.50		0.010		0.010
			380.50	382.00	D039052	1.50		<0.005		0.001
			382.00	383.50	D039054	1.50		0.008		0.008
			383.50	385.00	D039055	1.50		0.006		0.006
			385.00	386.50	D039056	1.50		0.168		0.168



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			386.50	388.00	D039057	1.50		0.275		0.275
			388.00	389.50	D039058	1.50		0.197		0.197
			389.50	391.00	D039059	1.50		0.469		0.469
			391.00	392.00	D039060	1.00		0.077		0.077
			392.00	393.30	D039061	1.30		0.631		0.631
			393.30	395.00	D039062	1.70		0.926		0.926
393.60	397.10	CB	395.00	396.00	D039064	1.00		0.498		0.498
		<b>Carbonaté</b>	396.00	397.20	D039065	1.20		0.582		0.582
		Passage très carbonaté et bréchifié.								
397.10	412.80	SY								
		<b>Syérite</b>								
		Peu de phénocristaux. Hématisée.								
397.10	466.00	HM	397.20	398.50	D039066	1.30		0.122		0.122
		<b>Hématisé</b>	398.50	400.00	D039067	1.50		0.312		0.312
		Généralement hématisé avec passage décimétriques chloritisés	400.00	401.50	D039068	1.50		0.117		0.117
		ou séricitisés.	401.50	403.00	D039069	1.50		0.298		0.298
			403.00	404.50	D039070	1.50		0.103		0.103
			404.50	406.00	D039071	1.50		1.025		1.025
			406.00	407.50	D039072	1.50		0.048		0.048
			407.50	409.00	D039074	1.50		0.019		0.019
			409.00	410.50	D039075	1.50		0.007		0.007
			410.50	412.00	D039076	1.50		<0.005		0.001
			412.00	413.50	D039077	1.50		0.101		0.101
			413.50	415.00	D039078	1.50		0.009		0.009
			415.00	416.50	D039079	1.50		0.028		0.028
			416.50	418.00	D039080	1.50		0.012		0.012
			418.00	419.50	D039081	1.50		0.282		0.282
			419.50	421.00	D039082	1.50		<0.005		0.001
			421.00	422.50	D039084	1.50		0.052		0.052
			422.50	424.00	D039085	1.50		0.008		0.008
			424.00	425.50	D039086	1.50		0.103		0.103
			425.50	427.00	D039087	1.50		0.025		0.025
			427.00	428.50	D039088	1.50		0.204		0.204

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
431.40	476.00	SY <b>Syénite</b> Peu de phénocristaux. Hématisée.	428.50	430.00	D039089	1.50	<0.005		0.001
			430.00	431.50	D039091	1.50	<0.005		0.001
			431.50	433.00	D039092	1.50	<0.005		0.001
			433.00	434.50	D039094	1.50	0.026		0.026
			434.50	436.00	D039095	1.50	0.046		0.046
435.50	435.80	FAI <b>Faille 25°</b> Zone de faille avec forte chloritisation, et lessivage du toit syénitique.	436.00	437.50	D039096	1.50	0.011		0.011
			437.50	439.00	D039097	1.50	<0.005		0.001
			439.00	440.50	D039098	1.50	0.051		0.051
			440.50	442.00	D039099	1.50	0.006		0.006
			442.00	443.50	D039100	1.50	<0.005		0.001
			443.50	445.00	D039101	1.50	0.555		0.555
			445.00	446.50	D039102	1.50	0.794		0.794
			446.50	448.00	D039104	1.50	0.392		0.392
			448.00	449.50	D039105	1.50	0.216		0.216
			449.50	451.00	D039106	1.50	0.071		0.071
			451.00	452.50	D039107	1.50	0.481		0.481
			452.50	454.00	D039108	1.50	0.038		0.038
			454.00	455.50	D039109	1.50	0.517		0.517
			455.50	457.00	D039110	1.50	0.984		0.984
			457.00	458.50	D039111	1.50	0.167		0.167
466.00	476.00	CH <b>Chloriteux</b> Avec passages légèrement hématisés. Unité carbonatée.	458.50	460.00	D039112	1.50	0.089		0.089
			460.00	461.50	D039114	1.50	0.095		0.095
			461.50	463.00	D039115	1.50	0.688		0.688
			463.00	464.50	D039116	1.50	0.144		0.144
			464.50	466.00	D039117	1.50	0.467		0.467
			466.00	467.70	D039118	1.70	0.515		0.515
			467.70	469.10	D039119	1.40	0.015		0.015
			469.10	470.50	D039120	1.40	0.006		0.006
			470.50	471.90	D039121	1.40	0.010		0.010
			471.90	473.50	D039122	1.60	0.482		0.482
473.50	475.00	D039124	1.50	1.050		1.050			
475.00	476.00	D039125	1.00	0.657		0.657			

476.00

Fin du sondage

Nombre d'échantillons : 315

Nombre d'échantillons QAQC : 45

Longueur totale échantillonnée : 466.00

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	14.50	D031770	M1	0.00	<0.005	0.001
17.50	17.50	D031773	L	0.00	2.030	2.030
31.00	32.50	D031783	D031782	1.50	0.024	0.024
44.50	44.50	D031793	M	0.00	3.070	3.070
58.00	59.50	D031803	D031802	1.50	<0.005	0.001
67.00	67.00	D031810	M1	0.00	<0.005	0.001
70.00	70.00	D031813	J	0.00	0.725	0.725
83.00	84.50	D031823	D031822	1.50	<0.005	0.001
97.00	97.00	D031833	K	0.00	1.075	1.075
110.50	112.00	D031843	D031842	1.50	0.007	0.007
119.00	119.00	D031850	M1	0.00	<0.005	0.001
122.00	122.00	D031853	L	0.00	2.190	2.190
136.00	137.50	D031863	D031862	1.50	<0.005	0.001
149.80	149.80	D031873	M	0.00	3.250	3.250
163.60	165.00	D031883	D031882	1.40	<0.005	0.001
171.50	171.50	D031890	M1	0.00	<0.005	0.001
174.00	174.00	D031893	J	0.00	0.726	0.726
186.00	186.90	D031903	D031902	0.90	<0.005	0.001
199.00	199.00	D031913	K	0.00	1.015	1.015
212.50	214.00	D031923	D031922	1.50	0.007	0.007
221.50	221.50	D031930	M1	0.00	<0.005	0.001
224.50	224.50	D031933	L	0.00	1.980	1.980
238.00	239.50	D031943	D031942	1.50	0.218	0.218
251.50	251.50	D031953	M	0.00	3.100	3.100
265.00	266.50	D031963	D031962	1.50	<0.005	0.001
274.00	274.00	D031970	M1	0.00	<0.005	0.001
277.00	277.00	D031973	J	0.00	0.736	0.736
290.50	292.00	D031983	D031982	1.50	0.024	0.024
304.00	304.00	D031993	K	0.00	1.135	1.135
317.00	318.50	D039003	D039002	1.50	0.179	0.179
326.00	326.00	D039010	M1	0.00	<0.005	0.001
329.00	329.00	D039013	J	0.00	0.770	0.770
342.30	344.00	D039023	D039022	1.70	0.006	0.006

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
355.00	355.00	D039033	K	0.00	1.010	1.010
368.50	370.00	D039043	D039042	1.50	0.198	0.198
377.50	377.50	D039050	M1	0.00	<0.005	0.001
380.50	380.50	D039053	L	0.00	2.090	2.090
393.30	395.00	D039063	D039062	1.70	0.928	0.928
406.00	406.00	D039073	M	0.00	3.110	3.110
419.50	421.00	D039083	D039082	1.50	0.006	0.006
428.50	428.50	D039090	M1	0.00	<0.005	0.001
431.50	431.50	D039093	J	0.00	0.763	0.763
445.00	446.50	D039103	D039102	1.50	0.441	0.441
458.50	458.50	D039113	K	0.00	1.045	1.045
471.90	473.50	D039123	D039122	1.60	0.482	0.482

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-199</b>	Titre minier :	Section :	630800
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Sylvain SAVADOGO	Du : 2010-05-06	Date de description :	2010-06-25
	Au : 2010-05-09		

Collet

Azimut : 180.00°  
 Plongée : -60.00°  
 Longueur : 261.30 m

UTM

Est	630 799.3
Nord	5 374 249.0
Élévation	303.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	345.10°	-59.10°	Oui
Reflex	8.00	319.00°	-59.10°	Oui
Reflex	11.00	324.40°	-59.20°	Oui
Reflex	14.00	322.50°	-59.10°	Oui
Reflex	17.00	311.60°	-59.00°	Oui
Reflex	20.00	180.00°	-58.50°	Non
Reflex	23.00	179.80°	-58.10°	Non
Reflex	26.00	179.00°	-57.70°	Non
Reflex	29.00	178.90°	-57.30°	Non
Reflex	32.00	178.70°	-57.10°	Non
Reflex	35.00	178.50°	-57.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	178.70°	-57.00°	Non
Reflex	41.00	178.80°	-57.00°	Non
Reflex	44.00	179.10°	-56.90°	Non
Reflex	47.00	179.10°	-56.90°	Non
Reflex	50.00	179.20°	-56.90°	Non
Reflex	53.00	179.50°	-56.90°	Non
Reflex	56.00	179.20°	-56.90°	Non
Reflex	59.00	179.80°	-56.90°	Non
Reflex	62.00	179.20°	-56.90°	Non
Reflex	65.00	179.80°	-56.90°	Non
Reflex	68.00	179.10°	-56.90°	Non
Reflex	71.00	179.70°	-56.90°	Non

Description

Saut de 3m à 84m, erreur de métrage; le profondeur linéaire totale est 261,3m.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	12.80	MT <b>Mort-terrain</b> MT						
12.80	58.00	BA <b>Basalte 50°</b> Basalte cisailé avec une altération graduelle; peu à plus ou moins sericitique et peu à plus ou moins silicifié, de 15 m à 28m; Dans REMBA, entre 28m et 58m, peu à plus ou moins silicifié, peu à plus ou moins sericitique, peu à modérément hématisé; Pyrite disséminé entre 0,5% et 0,8% dans la matrice et formant des veinules, entre 25.5m à 39m; Dyke de syénite porphyrique entre 42m et 45m;	12.80	14.00	D034588	1.20	0.037	0.037
			14.00	15.00	D034589	1.00	<0.005	0.001
12.80	28.00	CIS <b>Cisaillement</b> zone de cisaillement 50°AC;						
15.00	28.50	SR03; SI03 <b>Séricitique 3; Silicifié 3</b> peu à plus ou moins sericitique; peu à plus ou moins silicifié; altération météorique (lessivage par l'eau);	15.00	16.50	D034591	1.50	<0.005	0.001
			16.50	18.00	D034593	1.50	<0.005	0.001
			18.00	19.50	D034594	1.50	<0.005	0.001
			19.50	21.00	D034595	1.50	<0.005	0.001
			21.00	22.50	D034596	1.50	0.005	0.005
			22.50	24.00	D034597	1.50	0.008	0.008
			24.00	25.50	D034598	1.50	0.014	0.014
25.50	39.00	Py00.8 <b>Pyrite 0.8%</b> pyrite disséminée entre 0,5% et 0,8% dans la matrice et formant des veinules entre 25.5m à 39m;	25.50	27.00	D034599	1.50	1.315	1.315
			27.00	28.50	D034601	1.50	0.256	0.256
28.50	58.00	SI03; SR03; HM05 <b>Silicifié 3; Séricitique 3; Hématisé 5</b> plus ou moins silicifié; partiellement plus ou moins sericitisé; plus ou moins à modérément hématisé;	28.50	30.00	D034602	1.50	0.774	0.774
			30.00	31.50	D034603	1.50	1.600	1.600
			31.50	33.00	D034604	1.50	0.970	0.970
			33.00	34.50	D034605	1.50	2.070	2.070
			34.50	36.00	D034606	1.50	0.044	0.044
			36.00	37.50	D034607	1.50	2.670	2.670
			37.50	39.00	D034608	1.50	0.788	0.788
			39.00	40.50	D034609	1.50	1.485	1.485
			40.50	42.00	D034611	1.50	2.260	2.260
			42.00	43.50	D034612	1.50	0.586	0.586

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			43.50	45.00	D034613	1.50	0.492		0.492
			45.00	46.50	D034614	1.50	0.025		0.025
			46.50	48.00	D034615	1.50	2.110		2.110
			48.00	49.50	D034616	1.50	0.026		0.026
			49.50	51.00	D034617	1.50	0.683		0.683
			51.00	52.50	D034618	1.50	0.521		0.521
			52.50	54.00	D034619	1.50	0.022		0.022
			54.00	55.50	D034621	1.50	1.135		1.135
			55.50	57.00	D034622	1.50	0.034		0.034
			57.00	58.20	D034623	1.20	1.890		1.890
58.00	145.00	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique; phénocristaux grossier (sup 2mm) de quartz chloriteux et hématisé; Roche peu et modérément hématisée; pyrite disséminée jusqu'à 2% dans la matrice; contact graduel avec BA; contenant des vQz peu hématisées, 50*AC; Entre 93m et 94m, cataclase avec injection de quartz; Entre 141,9m et 142,4m, vQz-Ank peu hématisé et partiellement peu chloriteux et contenant de Mgt <1%;							
58.00	184.00	HM05; CH02 <b>Hématisé 5; Chloriteux 2</b> modérément hématisé; et partiellement peu chloriteux; les phénocristaux de quartz sont hématisés et chloriteux; et contenant des cheveux de chlorite;	58.55	60.00	D034624	1.45	0.103		0.103
			60.00	61.50	D034625	1.50	0.256		0.256
			61.50	63.00	D034626	1.50	0.085		0.085
			63.00	64.50	D034627	1.50	0.207		0.207
			64.50	66.00	D034628	1.50	0.007		0.007
			66.00	67.50	D034629	1.50	0.091		0.091
			67.50	69.00	D034631	1.50	0.041		0.041
			69.00	70.50	D034633	1.50	0.099		0.099
			70.50	72.00	D034634	1.50	0.046		0.046
			72.00	73.50	D034635	1.50	0.042		0.042
			73.50	75.00	D034636	1.50	0.055		0.055
			75.00	76.50	D034637	1.50	0.063		0.063
			76.50	78.00	D034638	1.50	0.021		0.021
			78.00	79.50	D034639	1.50	0.023		0.023
79.50	81.00	D034641	1.50	<0.005		0.001			
81.00	82.50	D034642	1.50	0.033		0.033			



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	82.50	84.00	D034643	1.50	0.028		0.028
	84.00	85.50	D034644	1.50	0.014		0.014
	85.50	87.00	D034645	1.50	0.020		0.020
	87.00	88.50	D034646	1.50	0.017		0.017
	88.50	90.00	D034647	1.50	0.025		0.025
	90.00	91.50	D034648	1.50	0.084		0.084
	91.50	93.00	D034649	1.50	0.060		0.060
	93.00	94.50	D034651	1.50	0.024		0.024
	94.50	96.00	D034652	1.50	0.109		0.109
	96.00	97.50	D034653	1.50	0.038		0.038
	97.50	99.00	D034654	1.50	0.036		0.036
	99.00	100.50	D034655	1.50	0.049		0.049
	100.50	102.00	D034656	1.50	0.085		0.085
	102.00	103.50	D034657	1.50	0.020		0.020
	103.50	105.00	D034658	1.50	0.021		0.021
	105.00	106.50	D034659	1.50	0.093		0.093
	106.50	108.00	D034661	1.50	0.041		0.041
	108.00	109.50	D034662	1.50	0.024		0.024
	109.50	111.00	D034663	1.50	0.211		0.211
	111.00	112.50	D034664	1.50	0.044		0.044
	112.50	114.00	D034665	1.50	0.121		0.121
	114.00	115.50	D034666	1.50	0.167		0.167
	115.50	117.00	D034667	1.50	0.178		0.178
	117.00	118.50	D034668	1.50	0.092		0.092
	118.50	120.00	D034669	1.50	0.111		0.111
	120.00	121.50	D034671	1.50	0.020		0.020
	121.50	123.00	D034673	1.50	0.029		0.029
	123.00	124.50	D034674	1.50	0.009		0.009
	124.50	126.00	D034675	1.50	0.026		0.026
	126.00	127.50	D034676	1.50	0.014		0.014
	127.50	129.00	D034677	1.50	0.135		0.135
	129.00	130.50	D034678	1.50	0.007		0.007
	130.50	132.00	D034679	1.50	0.016		0.016

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
145.00	184.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite porphyrique; phénocristaux grossier (sup 2mm) de quartz chloriteux et hématisé; modérément hématisé et peu chloriteux; pyrite disséminée jusqu'à 5% dans la matrice et les vQz; Zone contenant plusieurs vQz entre 40°AC et 55°AC;	132.00	133.50	D034681	1.50	0.007		0.007
			133.50	135.00	D034682	1.50	0.026		0.026
			135.00	136.50	D034683	1.50	<0.005		0.001
			136.50	138.00	D034684	1.50	0.005		0.005
			138.00	139.50	D034685	1.50	0.015		0.015
			139.50	141.00	D034686	1.50	<0.005		0.001
			141.00	142.50	D034687	1.50	<0.005		0.001
			142.50	144.00	D034688	1.50	0.030		0.030
			144.00	145.50	D034689	1.50	0.061		0.061
			145.50	147.00	D034691	1.50	0.157		0.157
			147.00	148.50	D034692	1.50	0.010		0.010
			148.50	150.00	D034693	1.50	0.106		0.106
			150.00	151.50	D034694	1.50	0.046		0.046
			151.50	153.00	D034695	1.50	0.053		0.053
			153.00	154.50	D034696	1.50	0.034		0.034
			154.50	156.00	D034697	1.50	0.022		0.022
			156.00	157.50	D034698	1.50	0.067		0.067
			157.50	159.00	D034699	1.50	0.102		0.102
			159.00	160.50	D034701	1.50	0.039		0.039
			160.50	162.00	D034702	1.50	0.009		0.009
			162.00	163.50	D034703	1.50	0.008		0.008
			163.50	165.00	D034704	1.50	0.180		0.180
			165.00	166.50	D034705	1.50	0.005		0.005
			166.50	168.00	D034706	1.50	0.006		0.006
			168.00	169.50	D034707	1.50	0.009		0.009
			169.50	171.00	D034708	1.50	0.005		0.005
171.00	172.50	D034709	1.50	<0.005		0.001			
172.50	174.00	D034711	1.50	<0.005		0.001			
174.00	175.50	D034713	1.50	0.005		0.005			
175.50	177.00	D034714	1.50	0.009		0.009			
177.00	178.50	D034715	1.50	0.012		0.012			
178.50	180.00	D034716	1.50	0.008		0.008			
180.00	181.50	D034717	1.50	0.005		0.005			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			181.50	183.00	D034718	1.50		0.008	
			183.00	184.50	D034719	1.50		<0.005	0.001
145.00	169.00	Py00.5 <b>Pyrite 0.5%</b> cristaux de pyrite disséminée dans la matrice et les vQz jusqu'à 0,5%;							
184.00	213.40	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique et silicifiée; phénocristaux grossier (sup 2mm) de quartz; Roche plus ou moins silicifiée, peu à plus ou moins carbonatée, faiblement à peu hématisée; pyrite disséminée jusqu'à 2% dans la matrice; Cette syénite est porphyrique comme l'unité lithologique précédente, et en plus elle est brechifiée par endroit avec des fragments arrondis de syénite;							
184.00	213.40	SI03; CB03 <b>Silicifié 3; Carbonaté 3</b> plus ou moins silicifié; plus ou moins carbonaté; la silicification est supérieure à la carbonatation;	184.50	186.00	D034721	1.50		0.010	0.010
			186.00	187.50	D034722	1.50		<0.005	0.001
			187.50	189.00	D034723	1.50		<0.005	0.001
			189.00	190.50	D034724	1.50		<0.005	0.001
			190.50	192.00	D034725	1.50		0.009	0.009
			192.00	193.50	D034726	1.50		<0.005	0.001
			193.50	195.00	D034727	1.50		<0.005	0.001
			195.00	196.50	D034728	1.50		<0.005	0.001
			196.50	198.00	D034729	1.50		<0.005	0.001
			198.00	199.50	D034731	1.50		<0.005	0.001
			199.50	201.00	D034732	1.50		<0.005	0.001
			201.00	202.50	D034733	1.50		<0.005	0.001
			202.50	204.00	D034734	1.50		<0.005	0.001
			204.00	205.50	D034735	1.50		<0.005	0.001
			205.50	207.00	D034736	1.50		<0.005	0.001
			207.00	208.50	D034737	1.50		<0.005	0.001
			208.50	210.00	D034738	1.50		<0.005	0.001
			210.00	211.70	D034739	1.70		<0.005	0.001
			211.70	213.40	D034741	1.70		<0.005	0.001
213.40	234.00	GR; FIN; MTY <b>Grès 40°; Grains fins; Grains moyens</b>	213.40	214.50	D034742	1.10		0.011	0.011

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
213.40	232.50	CB03 <b>Carbonaté 3</b> plus ou moins carbonaté	214.50	216.00	D034743	1.50	0.008		0.008
			216.00	217.50	D034744	1.50	0.010		0.010
			217.50	219.00	D034745	1.50	0.012		0.012
			219.00	220.50	D034746	1.50	0.010		0.010
			220.50	222.00	D034747	1.50	0.006		0.006
			222.00	223.50	D034748	1.50	0.013		0.013
			223.50	225.00	D034749	1.50	0.020		0.020
			225.00	226.50	D034751	1.50	0.028		0.028
			226.50	228.00	D034753	1.50	0.023		0.023
			228.00	229.50	D034754	1.50	0.012		0.012
			229.50	231.00	D034755	1.50	0.016		0.016
			231.00	232.50	D034756	1.50	0.030		0.030
			232.50	234.00	D034757	1.50	0.014		0.014
234.00	261.30	ST <b>Siltstone 40°</b> siltstone très peu à modérément carbonaté; partiellement peu à plus ou moins chloriteux; partiellement peu sericitique; contenant du graphite et de la fuchsite; contenant des vQz injecté dans la zone cisailée entre 246.6m et 261,3m, 40°AC;	234.00	235.50	D034758	1.50	0.020		0.020
			235.50	237.00	D034759	1.50	0.007		0.007
			237.00	238.50	D034761	1.50	0.169		0.169
			238.50	240.00	D034762	1.50	0.008		0.008
			240.00	241.50	D034763	1.50	0.008		0.008
241.50	246.60	CB05 <b>Carbonaté 5</b> plus ou moins à modérément carbonaté;	241.50	243.00	D034764	1.50	0.011		0.011
			243.00	244.50	D034765	1.50	0.006		0.006
			244.50	246.00	D034766	1.50	<0.005		0.001
			246.00	247.50	D034767	1.50	0.018		0.018
246.60	253.50	CB05; CH03; SR02 <b>Carbonaté 5; Chloriteux 3; Séricitique 2</b> modérément carbonaté; plus ou moins chloriteux; peu sericitique;							
246.60	261.30	CIS <b>Cisaillement 40°</b> cisaillement à 40°AC;							
246.60	261.30	Py05 <b>Pyrite 5%</b> pyrite disséminé entre 0,2% et 0,8% dans la matrice et les vQz	247.50	249.00	D034768	1.50	0.005		0.005
			249.00	250.50	D034769	1.50	<0.005		0.001
			250.50	252.00	D034771	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		injectés;	252.00	253.50	D034772	1.50	<0.005		0.001
253.50	259.50	CH03; SR02	253.50	255.00	D034773	1.50	<0.005		0.001
		<b>Chloriteux 3; Séricitique 2</b>	255.00	256.50	D034774	1.50	<0.005		0.001
		plus ou moins chloriteux et peu sericitique;	256.50	258.00	D034775	1.50	0.008		0.008
			258.00	259.50	D034776	1.50	<0.005		0.001
259.50	261.30	CB05	259.50	260.50	D034777	1.00	<0.005		0.001
		<b>Carbonaté 5</b>	260.50	261.30	D034778	0.80	<0.005		0.001
		modérément carbonaté;							
261.30	Fin du sondage								
	Nombre d'échantillons : 167								
	Nombre d'échantillons QAQC : 24								
	Longueur totale échantillonnée : 248.15								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	14.00	D034590	L	0.00	2.130	2.130
15.00	15.00	D034592	M1	0.00	<0.005	0.001
25.50	27.00	D034600	D034599	1.50	1.450	1.450
39.00	39.00	D034610	M	0.00	3.120	3.120
52.50	54.00	D034620	D034619	1.50	0.027	0.027
66.00	66.00	D034630	J	0.00	0.788	0.788
67.50	67.50	D034632	M1	0.00	<0.005	0.001
78.00	79.50	D034640	D034639	1.50	0.030	0.030
91.50	91.50	D034650	K	0.00	1.115	1.115
105.00	106.50	D034660	D034659	1.50	0.110	0.110
118.50	118.50	D034670	L	0.00	2.230	2.230
120.00	120.00	D034672	M1	0.00	0.006	0.006
130.50	132.00	D034680	D034679	1.50	0.017	0.017
144.00	144.00	D034690	M	0.00	3.280	3.280
157.50	159.00	D034700	D034699	1.50	0.145	0.145
171.00	171.00	D034710	J	0.00	0.734	0.734
172.50	172.50	D034712	M1	0.00	0.008	0.008
183.00	184.50	D034720	D034719	1.50	<0.005	0.001
196.50	196.50	D034730	K	0.00	1.010	1.010
210.00	211.50	D034740	D034739	1.50	<0.005	0.001
223.50	223.50	D034750	L	0.00	2.190	2.190
225.00	225.00	D034752	M1	0.00	<0.005	0.001
235.50	237.00	D034760	D034759	1.50	0.008	0.008
249.00	249.00	D034770	M	0.00	3.400	3.400

## Corporation Minière Osisko Div. Exploration

**Sondage :** BD10-200

Titre minier :

Section : 630300

Canton :

Niveau :

Foré par : Bradley et Frères

Rang :

Place de travail : Malartic

Décrit par : Sylvain SAVADOGO

Lot :

Du : 2010-04-28

Date de description : 2010-07-20

Au : 2010-04-30

Collet

UTM

Azimut : 0.00°

Plongée : -60.00°

Longueur : 173.00 m

Est 630 299.9

Nord 5 374 501.3

Élévation 294.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	0.00°	0.00°	Oui
Reflex	8.00	359.70°	-59.40°	Non
Reflex	11.00	1.30°	-59.40°	Non
Reflex	14.00	1.60°	-59.50°	Non
Reflex	17.00	0.90°	-59.50°	Non
Reflex	20.00	0.60°	-59.50°	Non
Reflex	23.00	2.20°	-59.50°	Non
Reflex	26.00	2.90°	-59.60°	Non
Reflex	29.00	2.90°	-59.60°	Non
Reflex	32.00	3.20°	-59.70°	Non
Reflex	35.00	0.40°	-59.70°	Non
Reflex	38.00	0.60°	-59.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	41.00	2.50°	-59.80°	Non
Reflex	44.00	2.00°	-59.80°	Non
Reflex	47.00	2.00°	-59.70°	Non
Reflex	50.00	1.20°	-59.60°	Non
Reflex	53.00	0.70°	-59.60°	Non
Reflex	56.00	1.20°	-59.50°	Non
Reflex	59.00	1.90°	-59.50°	Non
Reflex	62.00	2.10°	-59.50°	Non
Reflex	65.00	1.80°	-59.50°	Non
Reflex	68.00	1.50°	-59.50°	Non
Reflex	71.00	0.90°	-59.50°	Non
Reflex	74.00	359.80°	-59.50°	Non

Description

erreur de metrage entre 107m et 110: bloc de metrage erroné;

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	8.80	MT <b>Mort-terrain</b> MT						
8.80	56.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique avec de phénocristaux grossiers de FP hypodiomorphes; modérément carbonaté; modérément hématisée; entre 35m et 56, zone de transition entre la syénite et le dyke mafique (basalte), plus ou moins à modérément hématisé, peu et plus ou moins sericitique et peu à plus ou moins chloriteux; fin cristaux de pyrite disséminée entre 0,2 à 0,5% la matrice des passages sericitiques et chloriteux; contenant des veinules de Qz-CC; les contacts entres les zones sont graduels;	8.80	10.00	D045076	1.20	0.453	0.453
			10.00	11.00	D045077	1.00	0.930	0.930
			11.00	12.50	D045078	1.50	0.199	0.199
			12.50	14.00	D045079	1.50	0.140	0.140
			14.00	15.50	D045081	1.50	0.006	0.006
			15.50	17.00	D045082	1.50	0.043	0.043
			17.00	18.50	D045083	1.50	0.033	0.033
			18.50	20.00	D045084	1.50	<0.005	0.001
			20.00	21.50	D045085	1.50	0.009	0.009
			21.50	23.00	D045086	1.50	<0.005	0.001
			23.00	24.50	D045087	1.50	<0.005	0.001
			24.50	26.00	D045088	1.50	<0.005	0.001
			26.00	27.50	D045089	1.50	0.008	0.008
			27.50	29.00	D045091	1.50	<0.005	0.001
			29.00	30.50	D045092	1.50	0.026	0.026
			30.50	32.00	D045093	1.50	0.093	0.093
			32.00	33.50	D045094	1.50	<0.005	0.001
			33.50	35.00	D045095	1.50	0.018	0.018
8.80	35.00	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; modérément hématisé;						
35.00	56.00	CB05; HM05; SR03; CH03 <b>Carbonaté 5; Hématisé 5; Séricitique 3; Chloriteux 3</b> modérément carbonaté; non hématisé à modérément hématisé; peu à plus ou moins sericitique; peu à plus ou moins chloriteux;	35.00	36.50	D045096	1.50	0.206	0.206
			36.50	38.00	D045097	1.50	0.234	0.234
			38.00	39.50	D045098	1.50	0.007	0.007
			39.50	41.00	D045099	1.50	0.013	0.013
			41.00	42.50	D045101	1.50	0.109	0.109
			42.50	44.00	D045102	1.50	1.405	1.405
			44.00	45.50	D045103	1.50	0.016	0.016
			45.50	47.00	D045104	1.50	0.771	0.771
			47.00	48.50	D045105	1.50	0.863	0.863
			48.50	50.00	D045106	1.50	0.181	0.181



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
56.00	87.00	<b>BA</b> <b>Basalte</b> couloir de déformation; dyke mafique (basalte) dans une syénite; basalte cisailé, contenant quelques vQz-CC, 35°AC; modérément carbonaté; cristaux de pyrite disséminé dans la matrice entre 0,2% et 0,5%; contenant quelques zone syénitiques;	50.00	51.50	D045107	1.50	0.052		0.052
			51.50	53.00	D045108	1.50	0.991		0.991
			53.00	54.50	D045109	1.50	0.087		0.087
			54.50	56.00	D045111	1.50	0.376		0.376
56.00	87.00	<b>CB05</b> <b>Carbonaté 5</b> modérément carbonaté;							
56.00	87.00	<b>CIS</b> <b>Cisaillement 35°</b> cisailée à 35°AC	56.00	57.50	D045113	1.50	0.037		0.037
			57.50	59.00	D045114	1.50	0.030		0.030
			59.00	60.50	D045115	1.50	0.991		0.991
			60.50	62.00	D045116	1.50	0.315		0.315
			62.00	63.50	D045117	1.50	0.019		0.019
			63.50	65.00	D045118	1.50	0.018		0.018
			65.00	66.50	D045119	1.50	0.461		0.461
			66.50	68.00	D045121	1.50	1.775		1.775
			68.00	69.50	D045122	1.50	0.521		0.521
			69.50	71.00	D045123	1.50	0.097		0.097
			71.00	72.50	D045124	1.50	0.031		0.031
			72.50	74.00	D045125	1.50	0.030		0.030
			74.00	75.50	D045126	1.50	0.054		0.054
			75.50	77.00	D045127	1.50	0.082		0.082
			77.00	78.50	D045128	1.50	3.250		3.250
78.50	87.50	<b>Py00.8</b> <b>Pyrite 0.8%</b> fins cristaux de Py disséminée dans la matrice;	78.50	80.00	D045129	1.50	1.940		1.940
			80.00	81.50	D045131	1.50	0.394		0.394
			81.50	83.00	D045132	1.50	0.724		0.724
			83.00	84.50	D045133	1.50	0.747		0.747
			84.50	86.00	D045134	1.50	0.121		0.121
			86.00	87.50	D045135	1.50	0.355		0.355

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
87.00	153.00	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique avec de phénocristaux grossiers de FP; modérément carbonaté; des passages peu et plus ou moins sericitique et peu à plus ou moins chloriteux; fin cristaux de pyrite disséminée entre 0,2 à 0,8% la matrice des passages silicifiés, sericitiques et chloriteux; contenant quelques vQz-CC et des veinules de Qz-CC; les contacts entre les zones sont graduels;	87.50	89.00	D045136	1.50	0.006		0.006
			89.00	90.50	D045137	1.50	<0.005		0.001
			90.50	92.00	D045138	1.50	0.005		0.005
			92.00	93.50	D045139	1.50	<0.005		0.001
			93.50	95.00	D045141	1.50	0.005		0.005
			95.00	96.50	D045142	1.50	<0.005		0.001
			96.50	98.00	D045143	1.50	<0.005		0.001
			98.00	99.50	D045144	1.50	0.005		0.005
			99.50	101.00	D045145	1.50	<0.005		0.001
			101.00	102.50	D045146	1.50	0.007		0.007
			102.50	104.00	D045147	1.50	<0.005		0.001
			104.00	105.50	D045148	1.50	<0.005		0.001
			105.50	107.00	D045149	1.50	<0.005		0.001
			107.00	108.50	D045151	1.50	0.097		0.097
			108.50	110.00	D045153	1.50	0.055		0.055
			110.00	111.50	D045154	1.50	0.017		0.017
			111.50	113.00	D045155	1.50	0.033		0.033
			113.00	114.50	D045156	1.50	0.007		0.007
			114.50	116.00	D045157	1.50	0.008		0.008
			116.00	117.50	D045158	1.50	<0.005		0.001
117.50	119.00	D045159	1.50	0.024		0.024			
119.00	120.50	D045161	1.50	0.018		0.018			
120.50	122.00	D045162	1.50	0.050		0.050			
122.00	123.50	D045163	1.50	0.008		0.008			
123.50	125.00	D045164	1.50	0.061		0.061			
125.00	126.50	D045165	1.50	0.057		0.057			
126.50	128.00	D045166	1.50	0.304		0.304			
128.00	129.50	D045167	1.50	0.051		0.051			
129.50	131.00	D045168	1.50	0.232		0.232			
131.00	132.50	D045169	1.50	0.133		0.133			
132.50	134.00	D045171	1.50	0.040		0.040			
87.00	134.00	CB05; HM05; SR03; CH03 <b>Carbonaté 5; Hématisé 5; Séricitique 3; Chloriteux 3</b> modérément carbonaté; plus ou moins à modérément hématisé;							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
134.00	163.50	partiellement peu à plus ou moins sericitique; partiellement peu à plus ou moins chloriteux; SI05; CB05; SR03 <b>Silicifié 5; Carbonaté 5; Séricitique 3</b>	134.00	135.50	D045172	1.50	0.432		0.432
			135.50	137.00	D045173	1.50	0.308		0.308
137.00	164.00	modérément silicifié; modérément carbonaté; plus ou moins sericitique Py00.8 <b>Pyrite 0.8%</b> fin cristaux de Py disséminé dans la matrice;	137.00	138.50	D045174	1.50	0.194		0.194
			138.50	140.00	D045175	1.50	0.212		0.212
			140.00	141.50	D045176	1.50	0.398		0.398
			141.50	143.00	D045177	1.50	0.473		0.473
			143.00	144.50	D045178	1.50	0.750		0.750
			144.50	146.00	D045179	1.50	1.050		1.050
			146.00	147.50	D045181	1.50	1.185		1.185
			147.50	149.00	D045182	1.50	0.635		0.635
			149.00	150.50	D045183	1.50	1.720		1.720
			150.50	152.00	D045184	1.50	1.685		1.685
			152.00	153.00	D045185	1.00	1.700		1.700
153.00	154.00	BA <b>Basalte</b> REBA, silicifié et modérément carbonaté; minéralisée à la pyrite disséminée jusqu'à 0,8%;	153.00	154.00	D045186	1.00	6.650		6.650
154.00	155.50	OM <b>Ouverture minière</b> OM							
155.50	173.00	BA <b>Basalte</b> basalte en deux zones: - de 153m à 163,5m, REBA, silicifié et modérément carbonaté; minéralisée à la pyrite disséminée jusqu'à 0,8%; le contact avec la syénite est bréchifié; - de 163,5m à 173m, basalte modérément carbonaté et cisailé à 40°AC;  la roche est fracturée comme dans un SEAM de fracture;	155.50	157.00	D045187	1.50	6.990		6.990
			157.00	158.00	D045188	1.00	0.545		0.545
			158.00	159.50	D045189	1.50	2.840		2.840
			159.50	161.00	D045191	1.50	3.170		3.170
			161.00	162.50	D045193	1.50	0.914		0.914
163.50	173.00	CB05 <b>Carbonaté 5</b> modérément carbonaté;	164.00	165.50	D045195	1.50	0.013		0.013
			165.50	167.00	D045196	1.50	0.672		0.672
			167.00	168.50	D045197	1.50	0.367		0.367

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	168.50	170.00	D045198	1.50	0.006		0.006
	170.00	171.50	D045199	1.50	0.224		0.224
	171.50	173.00	D045201	1.50	1.840		1.840
<p>173.00      Fin du sondage                      Nombre d'échantillons : 110                      Nombre d'échantillons QAQC : 16                      Longueur totale échantillonnée : 162.70</p>							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.50	14.00	D045080	D045079	1.50	0.058	0.058
26.00	26.00	D045090	K	0.00	1.075	1.075
39.50	41.00	D045100	D045099	1.50	0.015	0.015
53.00	53.00	D045110	L	0.00	2.070	2.070
54.50	54.50	D045112	M1	0.00	0.006	0.006
65.00	66.50	D045120	D045119	1.50	0.468	0.468
78.50	78.50	D045130	M	0.00	3.270	3.270
92.00	93.50	D045140	D045139	1.50	<0.005	0.001
105.50	105.50	D045150	J	0.00	0.767	0.767
107.00	107.00	D045152	M1	0.00	<0.005	0.001
117.50	119.00	D045160	D045159	1.50	0.024	0.024
131.00	131.00	D045170	K	0.00	1.095	1.095
144.50	146.00	D045180	D045179	1.50	0.966	0.966
158.00	158.00	D045190	L	0.00	2.230	2.230
159.50	159.50	D045192	M1	0.00	0.011	0.011
170.00	171.50	D045200	D045199	1.50	0.128	0.128

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-201</b>	Titre minier :	Section :	630300
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley et frères	Lot :		
Décrit par : Sylvain SAVADOGO	Du : 2010-05-01	Date de description :	2010-06-30
	Au : 2010-05-03		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 175.20 m

UTM

Est	630 300.0
Nord	5 374 449.9
Élévation	291.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	0.00°	0.00°	Oui
Reflex	11.00	359.50°	-59.70°	Non
Reflex	14.00	359.80°	-59.70°	Non
Reflex	17.00	357.50°	-59.60°	Oui
Reflex	20.00	359.30°	-59.70°	Non
Reflex	23.00	0.30°	-59.80°	Non
Reflex	26.00	1.20°	-59.80°	Non
Reflex	29.00	1.60°	-59.90°	Non
Reflex	32.00	0.20°	-59.90°	Non
Reflex	35.00	359.80°	-59.80°	Non
Reflex	38.00	1.70°	-59.80°	Non
Reflex	41.00	0.90°	-59.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	2.20°	-59.80°	Non
Reflex	47.00	2.80°	-59.90°	Non
Reflex	50.00	3.20°	-59.90°	Non
Reflex	53.00	3.10°	-59.90°	Non
Reflex	56.00	2.00°	-60.00°	Non
Reflex	59.00	1.50°	-59.90°	Non
Reflex	62.00	1.30°	-60.00°	Non
Reflex	65.00	0.00°	-60.00°	Non
Reflex	68.00	0.90°	-60.10°	Non
Reflex	71.00	0.90°	-60.00°	Non
Reflex	74.00	3.10°	-60.10°	Non
Reflex	77.00	3.50°	-60.10°	Non

Description

saut de block à 59m: erreur de métrage; forage arrêté à 175,20m dans un DRIFT.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	8.00	MT; MT <b>Mort-terrain; Mort-terrain</b> MT						
8.00	101.85	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique; phénocristaux grossiers de Qz et FP hématisés; plus ou moins à modérément carbonaté; plus ou moins à modérément hématisé, avec des zones peu à plus ou moins chloritisée; pyrite disséminée entre 0,2% et 0,5% dans la matrice dans les zones chloritisées et dans la zone cataclasée;	8.00	9.50	D034847	1.50	<0.005	0.001
			9.50	11.00	D034848	1.50	0.007	0.007
8.00	11.00	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; modérément hématisé;						
11.00	13.50	CH03; CB05 <b>Chloriteux 3; Carbonaté 5</b> modérément carbonaté et plus ou moins chloriteux;						
11.00	13.50	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée entre 0,2% et 0,5% dans la matrice	11.00	12.50	D034849	1.50	0.015	0.015
			12.50	14.00	D034851	1.50	<0.005	0.001
13.50	52.50	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; plus ou moins à modérément hématisé;	14.00	15.50	D034852	1.50	<0.005	0.001
			15.50	17.00	D034853	1.50	<0.005	0.001
			17.00	18.00	D034854	1.00	<0.005	0.001
			18.00	19.10	D034855	1.10	<0.005	0.001
			19.30	20.20	D034856	0.90	<0.005	0.001
			20.20	21.50	D034857	1.30	<0.005	0.001
			21.50	23.00	D034858	1.50	<0.005	0.001
			23.00	24.50	D034859	1.50	<0.005	0.001
			24.50	26.00	D034861	1.50	<0.005	0.001
			26.00	27.50	D034862	1.50	<0.005	0.001
			27.50	29.00	D034863	1.50	<0.005	0.001
			29.00	30.50	D034864	1.50	<0.005	0.001
			30.50	32.00	D034865	1.50	<0.005	0.001
			32.00	33.50	D034866	1.50	<0.005	0.001
			33.50	35.00	D034867	1.50	<0.005	0.001
			35.00	36.50	D034868	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			36.50	38.00	D034869	1.50	<0.005		0.001
			38.00	39.50	D034871	1.50	0.006		0.006
			39.50	41.00	D034873	1.50	<0.005		0.001
			41.00	42.50	D034874	1.50	<0.005		0.001
			42.50	44.00	D034875	1.50	<0.005		0.001
			44.00	45.50	D034876	1.50	0.006		0.006
			45.50	47.00	D034877	1.50	<0.005		0.001
			47.00	48.50	D034878	1.50	<0.005		0.001
			48.50	50.00	D034879	1.50	0.677		0.677
			50.00	51.50	D034881	1.50	0.200		0.200
47.00	57.50	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée entre 0,2% et 0,5% dans la matrice;	51.50	53.00	D034882	1.50	0.006		0.006
			53.00	54.50	D034883	1.50	0.216		0.216
			54.50	56.00	D034884	1.50	0.006		0.006
52.50	55.00	CB05; CH03 <b>Carbonaté 5; Chloriteux 3</b> modérément carbonaté; plus ou moins chloriteux;	56.00	57.50	D034885	1.50	0.041		0.041
			57.50	59.00	D034886	1.50	<0.005		0.001
55.00	101.85	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; plus ou moins à modérément hématisé;	59.00	60.50	D034887	1.50	<0.005		0.001
			60.50	62.00	D034888	1.50	<0.005		0.001
			62.00	63.50	D034889	1.50	0.031		0.031
			63.50	65.00	D034891	1.50	0.005		0.005
			65.00	66.50	D034892	1.50	0.006		0.006
			66.50	68.00	D034893	1.50	0.007		0.007
			68.00	69.50	D034894	1.50	0.025		0.025
			69.50	71.00	D034895	1.50	0.049		0.049
			71.00	72.50	D034896	1.50	0.678		0.678
			72.50	74.00	D034897	1.50	0.013		0.013
69.50	74.00	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée entre 0,2% et 0,5% dans la matrice;	74.00	75.50	D034898	1.50	<0.005		0.001
			75.50	77.00	D034899	1.50	<0.005		0.001
			77.00	78.50	D034901	1.50	<0.005		0.001
			78.50	80.00	D034902	1.50	<0.005		0.001
			80.00	81.50	D034903	1.50	<0.005		0.001
			81.50	83.00	D034904	1.50	<0.005		0.001
			83.00	84.50	566502	1.50	<0.005		0.001
			84.50	86.00	566503	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			86.00	87.50	D034905	1.50	<0.005		0.001
			87.50	89.00	D034906	1.50	<0.005		0.001
			89.00	90.50	D034907	1.50	0.009		0.009
			90.50	92.00	D034908	1.50	<0.005		0.001
			92.00	93.50	D034909	1.50	0.013		0.013
			93.50	95.00	D034911	1.50	<0.005		0.001
			95.00	96.50	D034913	1.50	<0.005		0.001
			96.50	98.00	D034914	1.50	<0.005		0.001
			98.00	99.50	D034915	1.50	<0.005		0.001
			99.50	101.00	D034916	1.50	<0.005		0.001
			101.00	102.50	D034917	1.50	0.007		0.007
101.85	105.50	SY; POR <b>Syénite 50*; Porphyrique</b> syénite porphyrique; modérément chloriteuse; fantôme de phénocristaux de Qz-CC et FP-CC héamatisées; pyrite disséminé jusqu'à 0,5% dans la matrice; contenant des vQz héamatisées, 50*AC; le contact de cette unité litho est graduel;							
101.85	105.50	CH05; CB05 <b>Chloriteux 5; Carbonaté 5</b> modérément chloriteux; modérément carbonaté;							
101.85	105.50	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminé entre 0,2 et 0,5% dans la matrice et les vQz-CC;	102.50	104.00	D034918	1.50	0.020		0.020
			104.00	105.50	D034919	1.50	0.005		0.005
105.50	175.20	SY; POR <b>Syénite 50*; Porphyrique</b> syénite porphyrique; phénocristaux grossiers de Qz et FP héamatisés; plus ou moins à modérément carbonaté; plus ou moins à modérément héamatisé, avec des zones peu à plus ou moins chloritisée; pyrite disséminée entre 0,2% et 0,5% dans la matrice dans les zones chloritisées;	105.50	107.00	D034921	1.50	<0.005		0.001
			107.00	108.50	D034922	1.50	0.010		0.010
			108.50	110.00	D034923	1.50	<0.005		0.001
			110.00	111.50	D034924	1.50	<0.005		0.001
			111.50	113.00	D034925	1.50	0.005		0.005
			113.00	114.50	D034926	1.50	0.005		0.005
			114.50	116.00	D034927	1.50	<0.005		0.001
			116.00	117.50	D034928	1.50	<0.005		0.001
			117.50	119.00	D034929	1.50	<0.005		0.001
			119.00	120.50	D034931	1.50	0.005		0.005
			120.50	122.00	D034932	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			122.00	123.50	D034933	1.50	<0.005		0.001
			123.50	125.00	D034934	1.50	<0.005		0.001
			125.00	126.50	D034935	1.50	<0.005		0.001
			126.50	128.00	D034936	1.50	0.006		0.006
			128.00	129.50	D034937	1.50	<0.005		0.001
			129.50	131.00	D034938	1.50	<0.005		0.001
			131.00	132.50	D034939	1.50	<0.005		0.001
			132.50	134.00	D034941	1.50	<0.005		0.001
			134.00	135.50	D034942	1.50	0.011		0.011
			135.50	137.00	D034943	1.50	<0.005		0.001
			137.00	138.50	D034944	1.50	0.034		0.034
			138.50	140.00	D034945	1.50	<0.005		0.001
			140.00	141.50	D034946	1.50	<0.005		0.001
			141.50	143.00	D034947	1.50	0.022		0.022
			143.00	144.50	D034948	1.50	0.010		0.010
			144.50	146.00	D034949	1.50	<0.005		0.001
			146.00	147.50	D034951	1.50	<0.005		0.001
			147.50	149.00	D034953	1.50	<0.005		0.001
			149.00	150.50	D034954	1.50	<0.005		0.001
			150.50	152.00	D034955	1.50	<0.005		0.001
			152.00	153.50	D034956	1.50	<0.005		0.001
			153.50	155.00	D034957	1.50	0.168		0.168
			155.00	156.50	D034958	1.50	0.274		0.274
			156.50	158.00	D034959	1.50	1.045		1.045
105.50	158.00	CB05; CH02 <b>Carbonaté 5; Chloriteux 2</b> plus ou moins à modérément carbonaté; partiellement peu chloriteux;							
158.00	161.00	CB05; HM03; CH02 <b>Carbonaté 5; Hématisé 3; Chloriteux 2</b> modérément carbonaté; plus ou moins hématisé; très peu à peu chloriteux;	158.00	159.50	D034961	1.50	1.380		1.380
			159.50	161.00	D034962	1.50	0.565		0.565
161.00	168.40	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carnaté; modérément hématisé;	161.00	162.50	D034963	1.50	0.022		0.022
			162.50	164.00	D034964	1.50	0.020		0.020
			164.00	165.50	D034965	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
168.40	175.20	CB05; CH03; CH05 <b>Carbonaté 5; Chloriteux 3; Chloriteux 5</b> modérment carbonaté; très peu à plus ou moins chloriteux; partiellement plus ou moins à modérément hématisé;	165.50	167.00	D034966	1.50	<0.005		0.001
			167.00	168.50	D034967	1.50	0.023		0.023
			168.50	170.00	D034968	1.50	<0.005		0.001
			170.00	171.50	D034969	1.50	<0.005		0.001
			171.50	173.00	D034971	1.50	<0.005		0.001
			173.00	174.00	D034972	1.00	<0.005		0.001
			174.00	175.20	D034973	1.20	<0.005		0.001
175.20	Fin du sondage Nombre d'échantillons : 113 Nombre d'échantillons QAQC : 16 Longueur totale échantillonnée : 167.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
11.00	11.00	D034850	M	0.00	3.130	3.130
23.00	24.50	D034860	D034859	1.50	0.005	0.005
36.50	36.50	D034870	J	0.00	0.782	0.782
38.00	38.00	D034872	M1	0.00	<0.005	0.001
48.50	50.00	D034880	D034879	1.50	0.788	0.788
62.00	62.00	D034890	K	0.00	1.065	1.065
75.50	77.00	D034900	D034899	1.50	<0.005	0.001
92.00	92.00	D034910	L	0.00	2.310	2.310
93.50	93.50	D034912	M1	0.00	<0.005	0.001
104.00	105.50	D034920	D034919	1.50	0.005	0.005
117.50	117.50	D034930	M	0.00	3.000	3.000
131.00	132.50	D034940	D034939	1.50	0.005	0.005
144.50	144.50	D034950	J	0.00	0.764	0.764
146.00	146.00	D034952	M1	0.00	<0.005	0.001
156.50	158.00	D034960	D034959	1.50	0.772	0.772
170.00	170.00	D034970	K	0.00	1.065	1.065

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-202**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Johan Bergé

Lot :

Du :                      2010-05-01

Date de description :

Au :                      2010-05-02

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -67.00°  
 Longueur :                      144.00 m

Est	631 100.2
Nord	5 374 554.7
Élévation	282.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	337.60°	-67.00°	Oui
Reflex	9.00	338.40°	-66.50°	Oui
Reflex	12.00	317.40°	-66.40°	Oui
Reflex	15.00	358.90°	-66.30°	Non
Reflex	18.00	358.80°	-66.60°	Non
Reflex	21.00	358.70°	-66.60°	Non
Reflex	24.00	0.40°	-67.00°	Non
Reflex	27.00	358.40°	-66.70°	Non
Reflex	30.00	0.80°	-66.60°	Non
Reflex	33.00	0.50°	-66.50°	Non
Reflex	36.00	0.50°	-66.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	0.50°	-66.40°	Non
Reflex	42.00	0.60°	-66.30°	Non
Reflex	45.00	0.60°	-66.30°	Non
Reflex	48.00	0.30°	-66.30°	Non
Reflex	51.00	0.20°	-66.30°	Non
Reflex	54.00	0.30°	-66.30°	Non
Reflex	57.00	360.00°	-66.30°	Non
Reflex	60.00	359.80°	-66.30°	Non
Reflex	63.00	359.90°	-66.40°	Non
Reflex	66.00	359.70°	-66.20°	Non
Reflex	69.00	359.80°	-66.30°	Non
Reflex	72.00	0.10°	-66.30°	Non

Description

Oubli d'un bloc entre 93m et 96m (mesure 6m). Ajout systématique de 3m à partir du bloc 96m (en réalité 99m).  
 Nouveau EOH=144m.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	15.00	MT <b>Mort-terrain</b> Pas de récupération.						
15.00	17.00	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique. Yeux de quartz visible par endroit. Pas de hyaloclatite, coulée massive.						
15.00	144.00	CH <b>Chloriteux</b> Tout le trou est chloritisé.	15.00	16.00	D039537	1.00	0.015	0.015
			16.00	17.00	D039538	1.00	0.011	0.011
17.00	18.00	NR <b>Carotte perdue</b> Pas de récupération.						
18.00	20.10	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique. Yeux de quartz visible par endroit. Pas de hyaloclatite, coulée massive.	18.00	19.00	D039539	1.00	0.129	0.129
			19.00	20.10	D039540	1.10	2.720	2.720
20.10	21.00	NR <b>Carotte perdue</b> Pas de récupération.						
21.00	22.70	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique. Yeux de quartz visible par endroit. Pas de hyaloclatite, coulée massive.	21.00	22.70	D039541	1.70	1.770	1.770
22.70	23.90	NR <b>Carotte perdue</b> Pas de récupération.						
23.90	82.30	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique.	23.90	25.50	D039542	1.60	>10.0	15.10
			25.50	26.60	D039544	1.10	>10.0	21.60
			26.60	27.80	D039545	1.20	6.070	6.070

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		Yeux de quartz visible par endroit.	27.80	29.50	D039546	1.70		5.060	5.060
		Pas de hyaloclatite, coulée massive.	29.50	31.00	D039547	1.50		4.560	4.560
			31.00	32.70	D039548	1.70		2.140	2.140
			32.70	34.00	D039549	1.30		2.040	2.040
			34.00	35.50	D039550	1.50		7.330	7.330
			35.50	37.00	D039551	1.50		5.680	5.680
			37.00	38.50	D039552	1.50		0.103	0.103
			38.50	40.00	D039554	1.50		0.030	0.030
			40.00	41.50	D039555	1.50		0.005	0.005
			41.50	43.00	D039556	1.50		<0.005	0.001
			43.00	44.50	D039557	1.50		<0.005	0.001
			44.50	46.00	D039558	1.50		0.005	0.005
			46.00	47.50	D039559	1.50		<0.005	0.001
			47.50	49.00	D039560	1.50		0.007	0.007
			49.00	50.50	D039561	1.50		<0.005	0.001
			50.50	52.00	D039562	1.50		<0.005	0.001
			52.00	53.50	D039564	1.50		<0.005	0.001
			53.50	54.50	D039565	1.00		<0.005	0.001
			54.50	55.40	D039566	0.90		<0.005	0.001
			55.40	57.00	D039567	1.60		<0.005	0.001
56.00	59.00	FRC	57.00	58.50	D039568	1.50		0.012	0.012
		<b>Fracturé</b>	58.50	60.20	D039569	1.70		<0.005	0.001
		Zone de faille complètement broyée.	60.20	61.10	D039571	0.90		<0.005	0.001
			61.10	62.10	D039572	1.00		<0.005	0.001
			62.10	63.50	D039574	1.40		0.016	0.016
63.50	71.20	FRC	63.50	65.00	D039575	1.50		<0.005	0.001
		<b>Fracturé</b>	65.00	66.50	D039576	1.50		<0.005	0.001
		Zone faillée complètement broyée.	66.50	68.00	D039577	1.50		0.012	0.012
			68.00	69.50	D039578	1.50		0.010	0.010
			69.50	71.00	D039579	1.50		0.025	0.025
			71.00	72.50	D039580	1.50		<0.005	0.001
			72.50	74.00	D039581	1.50		<0.005	0.001
			74.00	75.50	D039582	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
82.30	84.70	GA <b>Gabbro</b> Gabbro à grain moyen et phénocristaux de feldspath.	75.50	77.00	D039584	1.50	<0.005		0.001			
			77.00	78.50	D039585	1.50	<0.005		0.001			
			78.50	80.00	D039586	1.50	<0.005		0.001			
			80.00	80.90	D039587	0.90	<0.005		0.001			
			80.90	82.30	D039588	1.40	<0.005		0.001			
			82.30	83.80	D039589	1.50	<0.005		0.001			
			83.80	84.70	D039590	0.90	<0.005		0.001			
			84.70	100.50	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique. Yeux de quartz visible par endroit. Pas de hyaloclatite, coulée massive.	84.70	86.00	D039591	1.30	<0.005		0.001
86.00	87.50	D039592				1.50	<0.005		0.001			
87.50	89.20	D039594				1.70	<0.005		0.001			
89.20	90.00	D039595				0.80	<0.005		0.001			
89.50	91.80	FAI <b>Faïlle</b> Zone faillée.				90.00	91.40	D039596	1.40	<0.005		0.001
			91.40	93.00	D039597	1.60	<0.005		0.001			
			93.00	94.50	D039598	1.50	<0.005		0.001			
			94.50	96.00	D039599	1.50	<0.005		0.001			
			96.00	97.50	D039600	1.50	<0.005		0.001			
			97.50	99.00	D039601	1.50	<0.005		0.001			
			99.00	100.50	D039602	1.50	<0.005		0.001			
100.50	112.50	GA <b>Gabbro</b> Gabbro à grain moyen et phénocristaux de feldspath.	100.50	102.00	D039604	1.50	<0.005		0.001			
			102.00	103.50	D039605	1.50	<0.005		0.001			
			103.50	105.00	D039606	1.50	0.023		0.023			
			105.00	106.50	D039607	1.50	<0.005		0.001			
			106.50	108.00	D039608	1.50	<0.005		0.001			
			108.00	109.50	D039609	1.50	<0.005		0.001			
			109.50	111.00	D039611	1.50	<0.005		0.001			
			111.00	112.50	D039612	1.50	<0.005		0.001			
			112.50	144.00	BA <b>Basalte</b> Basalte très fracturé. Altération chloritique. Yeux de quartz visible par endroit. Pas de hyaloclatite, coulée massive.	112.50	114.00	D039614	1.50	<0.005		0.001
						114.00	115.50	D039615	1.50	<0.005		0.001
115.50	117.00	D039616				1.50	<0.005		0.001			
117.00	117.90	D039617				0.90	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
117.90	123.00	FAI	117.90	119.00	D039618	1.10	<0.005		0.001
		<b>Faille</b>	119.00	120.00	D039619	1.00	<0.005		0.001
		Zone faillée extrêmement fracturée, non carbonatée.	120.00	121.50	D039620	1.50	<0.005		0.001
			121.50	123.00	D039621	1.50	<0.005		0.001
			123.00	124.50	D039622	1.50	<0.005		0.001
			124.50	126.00	D039624	1.50	<0.005		0.001
			126.00	127.50	D039625	1.50	<0.005		0.001
			127.50	129.00	D039626	1.50	<0.005		0.001
			129.00	130.50	D039627	1.50	<0.005		0.001
			130.50	132.00	D039628	1.50	<0.005		0.001
			132.00	133.50	D039629	1.50	<0.005		0.001
			133.50	135.00	D039630	1.50	<0.005		0.001
			135.00	136.50	D039631	1.50	<0.005		0.001
			136.50	138.00	D039632	1.50	<0.005		0.001
			138.00	139.50	D039634	1.50	<0.005		0.001
			139.50	141.00	D039635	1.50	<0.005		0.001
			141.00	142.50	D039636	1.50	<0.005		0.001
			142.50	144.00	D039637	1.50	<0.005		0.001
144.00	Fin du sondage								
	Nombre d'échantillons : 89								
	Nombre d'échantillons QAQC : 12								
	Longueur totale échantillonnée : 125.90								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
23.90	25.50	D039543	D039542	1.60	>10.0	15.100
37.00	37.00	D039553	M	0.00	3.080	3.080
50.50	52.00	D039563	D039562	1.50	<0.005	0.001
58.50	58.50	D039570	M1	0.00	<0.005	0.001
61.10	61.10	D039573	J	0.00	0.749	0.749
74.00	75.50	D039583	D039582	1.50	<0.005	0.001
86.00	86.00	D039593	K	0.00	1.130	1.130
99.00	100.50	D039603	D039602	1.50	<0.005	0.001
108.00	108.00	D039610	M1	0.00	<0.005	0.001
111.00	111.00	D039613	L	0.00	2.250	2.250
123.00	124.50	D039623	D039622	1.50	<0.005	0.001
136.50	136.50	D039633	M	0.00	3.240	3.240

## Corporation Minière Osisko Div. Exploration

**Sondage :** BD10-203

Titre minier :

Section : 631000

Canton :

Niveau :

Foré par : Bradley

Rang :

Place de travail : Malartic

Décrit par : Sylvain SAVADOGO

Lot :

Du : 2010-05-02

Date de description : 2010-06-22

Au : 2010-05-03

Collet

UTM

Azimut : 0.00°  
 Plongée : -74.00°  
 Longueur : 195.00 m

Est	631 000.1
Nord	5 374 575.0
Élévation	282.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	320.60°	-73.80°	Oui
Reflex	9.00	316.80°	-73.80°	Oui
Reflex	12.00	1.40°	-73.90°	Non
Reflex	15.00	1.40°	-73.90°	Non
Reflex	18.00	1.40°	-74.00°	Non
Reflex	21.00	1.30°	-74.00°	Non
Reflex	24.00	1.40°	-74.10°	Non
Reflex	27.00	1.50°	-74.10°	Non
Reflex	30.00	1.50°	-74.00°	Non
Reflex	33.00	1.10°	-73.90°	Non
Reflex	36.00	0.90°	-74.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	0.60°	-74.00°	Non
Reflex	42.00	0.40°	-74.00°	Non
Reflex	45.00	0.10°	-74.00°	Non
Reflex	48.00	359.80°	-73.90°	Non
Reflex	51.00	359.70°	-73.90°	Non
Reflex	54.00	359.60°	-73.90°	Non
Reflex	57.00	359.50°	-73.90°	Non
Reflex	60.00	359.30°	-73.80°	Non
Reflex	63.00	359.30°	-73.80°	Non
Reflex	66.00	359.40°	-73.90°	Non
Reflex	69.00	359.30°	-73.80°	Non
Reflex	72.00	359.30°	-73.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	9.90	MT <b>Mort-terrain</b> MT							
9.90	33.00	SY; POR; BRI <b>Syénite 35°; Porphyrique; Brèche intrusive</b> syénite partiellement porphyrique et partiellemt brechifié; peu à plus ou moins chloriteux; peu à plus ou moins hématisé; plus ou moins carbonaté; pyrite disséminé entre 0,2% et 0,5%; contenant une veine de quartz calcite, 30°AC; contact scisaillé 30°AC entre SY et BA;							
9.90	33.00	HM03; CB03; CH03 <b>Hématisé 3; Carbonaté 3; Chloriteux 3</b> peu à plus moins hématisé; plus ou moins carbonaté; peu à plus ou moins chloriteux;	9.90	11.00	D034446	1.10	0.522		0.522
			11.00	12.00	D034447	1.00	0.273		0.273
			12.00	13.50	D034448	1.50	0.131		0.131
			13.50	15.00	D034449	1.50	0.314		0.314
			15.00	16.50	D034451	1.50	0.178		0.178
			16.50	18.00	D034452	1.50	0.173		0.173
			18.00	19.50	D034453	1.50	0.562		0.562
			19.50	21.00	D034454	1.50	0.272		0.272
			21.00	22.50	D034455	1.50	0.588		0.588
			22.50	24.00	D034456	1.50	1.255		1.255
			24.00	25.50	D034457	1.50	1.800		1.800
			25.50	27.00	D034458	1.50	0.997		0.997
			27.00	28.50	D034459	1.50	1.725		1.725
			28.50	30.00	D034461	1.50	1.195		1.195
			30.00	31.50	D034462	1.50	1.345		1.345
			31.50	33.00	D034463	1.50	3.710		3.710
9.90	30.00	Py00.5 <b>Pyrite 0.5%</b> pyrite entre 0,2% et 0,5%							
33.00	84.15	BA; COU <b>Basalte 30°; Coussiné</b> BA, plus ou moins carbonaté; sericitisé dans les bordure de pillow; pyrite disséminée jusqu'à 0,2%; contact 15-20°AC, graduel avec SY;	33.00	34.50	D034464	1.50	2.010		2.010
			34.50	36.00	D034465	1.50	0.009		0.009
			36.00	37.50	D034466	1.50	0.007		0.007
			37.50	39.00	D034467	1.50	3.730		3.730
			39.00	40.50	D034468	1.50	0.378		0.378
			40.50	42.00	D034469	1.50	0.020		0.020
			42.00	43.50	D034471	1.50	0.790		0.790

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
33.00	45.00	CB03 <b>Carbonaté 3</b> plus ou moincarbonaté	43.50	45.00	D034473	1.50	0.009		0.009
45.00	84.15	CB05 <b>Carbonaté 5</b> modérément carbonaté	45.00	46.50	D034474	1.50	0.005		0.005
			46.50	48.00	D034475	1.50	0.005		0.005
			48.00	49.50	D034476	1.50	0.005		0.005
			49.50	51.00	D034477	1.50	<0.005		0.001
			51.00	52.50	D034478	1.50	<0.005		0.001
			52.50	54.00	D034479	1.50	<0.005		0.001
			54.00	55.50	D034481	1.50	<0.005		0.001
			55.50	57.00	D034482	1.50	<0.005		0.001
			57.00	58.50	D034483	1.50	<0.005		0.001
			58.50	60.00	D034484	1.50	<0.005		0.001
			60.00	61.50	D034485	1.50	<0.005		0.001
			61.50	63.00	D034486	1.50	<0.005		0.001
			63.00	64.50	D034487	1.50	<0.005		0.001
			64.50	66.00	D034488	1.50	<0.005		0.001
			66.00	67.50	D034489	1.50	<0.005		0.001
			67.50	69.00	D034491	1.50	<0.005		0.001
			69.00	70.50	D034492	1.50	<0.005		0.001
			70.50	72.00	D034493	1.50	<0.005		0.001
			72.00	73.50	D034494	1.50	<0.005		0.001
			73.50	75.00	D034495	1.50	<0.005		0.001
			75.00	76.50	D034496	1.50	<0.005		0.001
			76.50	78.00	D034497	1.50	<0.005		0.001
			78.00	79.50	D034498	1.50	<0.005		0.001
			79.50	81.00	D034499	1.50	<0.005		0.001
			81.00	82.50	D034501	1.50	<0.005		0.001
			82.50	84.15	D034502	1.65	<0.005		0.001
84.15	136.70	SY; POR <b>Syénite 40°; Porphyrique</b> syénite porhyrique avec des phénocristaux grossiers (2mm-1cm) de quartz-calcite; plus ou moins à modérément carbonaté, peu chloritisé partiellement peu sericitisé et peu hématisé; partiellement peu à plus ou	84.15	85.50	D034503	1.35	<0.005		0.001
			85.50	87.00	D034504	1.50	<0.005		0.001
			87.00	88.50	D034505	1.50	<0.005		0.001
			88.50	90.00	D034506	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
moins magnétisé; cristaux de pyrite disséminé jusqu'à 0,2%; contenant des sections de BA; contact nets;			90.00	91.50	D034507	1.50	<0.005		0.001
			91.50	93.00	D034508	1.50	<0.005		0.001
			93.00	94.50	D034509	1.50	<0.005		0.001
			94.50	96.00	D034511	1.50	<0.005		0.001
			96.00	97.50	D034513	1.50	<0.005		0.001
			97.50	99.00	D034514	1.50	<0.005		0.001
			99.00	100.50	D034515	1.50	<0.005		0.001
			100.50	102.00	D034516	1.50	<0.005		0.001
			102.00	103.50	D034517	1.50	<0.005		0.001
			103.50	105.00	D034518	1.50	<0.005		0.001
			105.00	106.50	D034519	1.50	<0.005		0.001
106.50	108.00	D034521	1.50	<0.005		0.001			
84.15	107.00	CB03; CH02; SR02; SR <b>Carbonaté 3; Chloriteux 2; Séricitique 2; Séricitique</b> plus ou moins carbonaté; peu chloriteux; partiellement peu sericitique;							
107.00	144.90	CB05; CH03; HM02 <b>Carbonaté 5; Chloriteux 3; Hématisé 2</b> modérément carbonaté; peu à plus ou moins chloriteux; peu hématisé;	108.00	109.50	D034522	1.50	0.007		0.007
			109.50	111.00	D034523	1.50	<0.005		0.001
			111.00	112.50	D034524	1.50	<0.005		0.001
			112.50	114.00	D034525	1.50	0.007		0.007
			114.00	115.50	D034526	1.50	<0.005		0.001
			115.50	117.00	D034527	1.50	0.020		0.020
			117.00	118.50	D034528	1.50	0.007		0.007
			118.50	120.00	D034529	1.50	<0.005		0.001
			120.00	121.50	D034531	1.50	0.006		0.006
			121.50	123.00	D034532	1.50	0.007		0.007
			123.00	124.50	D034533	1.50	0.005		0.005
			124.50	126.00	D034534	1.50	<0.005		0.001
			126.00	127.50	D034535	1.50	<0.005		0.001
			127.50	129.00	D034536	1.50	<0.005		0.001
			129.00	130.50	D034537	1.50	0.005		0.005
			130.50	132.00	D034538	1.50	<0.005		0.001
			132.00	133.50	D034539	1.50	<0.005		0.001
133.50	139.50	FAI	133.50	135.00	D034541	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		<b>Faille 35°</b> zone de faille et roche fracture; perte de carotte;	135.00	136.70	D034542	1.70	<0.005		0.001
136.70	137.20	NR							
		<b>Carotte perdue</b> LOST							
137.20	144.90	SY; POR	137.20	138.00	D034543	0.80	<0.005		0.001
		<b>Syénite 40°; Porphyrique</b> syénite porphyrique avec des phénocristaux grossiers (2mm-1cm) de quartz-calcite; modérément carbonaté, peu chloritisé partiellement peu sericitisé et peu hématisé; zone de fracture avec 50cm de perte de carotte entre 136,7m et 137,2m; cristaux de pyrite disséminé jusqu'à 0,2%; contenant des vQz-Tour dans la zone de veines; contact net avec le BA, 60°AC;	138.00	139.50	D034544	1.50	<0.005		0.001
			139.50	141.00	D034545	1.50	<0.005		0.001
			141.00	142.50	D034546	1.50	<0.005		0.001
			142.50	144.00	D034547	1.50	<0.005		0.001
			144.00	144.90	D034548	0.90	<0.005		0.001
144.90	195.00	BA; COU	144.90	146.00	D034549	1.10	<0.005		0.001
		<b>Basalte 60°; Coussiné</b> basalte coussiné, plus ou moins à modérément carbonaté; pyrite disséminé jusqu'à 0,2%; entre 183m et 186m, PyPo disséminé dans les vQz-CC; contenant des zone de failles à partir de 181m;	146.00	147.00	D034551	1.00	<0.005		0.001
			147.00	148.50	D034553	1.50	<0.005		0.001
			148.50	150.00	D034554	1.50	<0.005		0.001
			150.00	151.50	D034555	1.50	<0.005		0.001
			151.50	153.00	D034556	1.50	<0.005		0.001
144.90	146.00	CB05							
		<b>Carbonaté 5</b> modérément carbonaté							
153.00	154.50	Py00.8	153.00	154.50	D034557	1.50	<0.005		0.001
		<b>Pyrite 0.8%</b> pyrite disséminé entre 0,5% et 0,8% dans la matrice et les veines de vQz 30°QC;	154.50	156.00	D034558	1.50	<0.005		0.001
			156.00	157.50	D034559	1.50	<0.005		0.001
			157.50	159.00	D034561	1.50	<0.005		0.001
			159.00	160.50	D034562	1.50	<0.005		0.001
160.50	195.00	CB05	160.50	162.00	D034563	1.50	<0.005		0.001
		<b>Carbonaté 5</b> plus ou moins à modérément carbonaté	162.00	163.50	D034564	1.50	0.005		0.005
			163.50	165.00	D034565	1.50	0.008		0.008
			165.00	166.50	D034566	1.50	<0.005		0.001
			166.50	168.00	D034567	1.50	0.005		0.005
			168.00	169.50	D034568	1.50	<0.005		0.001
			169.50	171.00	D034569	1.50	<0.005		0.001
			171.00	172.50	D034571	1.50	<0.005		0.001
			172.50	174.00	D034572	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			174.00	175.50	D034573	1.50		0.005		0.005
			175.50	177.00	D034574	1.50		0.007		0.007
			177.00	178.50	D034575	1.50		0.008		0.008
			178.50	180.00	D034576	1.50		<0.005		0.001
			180.00	181.50	D034577	1.50		0.007		0.007
			181.50	183.00	D034578	1.50		<0.005		0.001
181.70	181.95	FAI <b>Faille</b> zone de faille; pas possible de prendre un angle								
183.00	186.00	Py00.2; PO00.2 <b>Pyrite 0.2%; Pyrrhotite 0.2%</b> Py-Po disséminé dans les vQz-CC, 50*AC;	183.00	184.50	D034579	1.50		0.011		0.011
			184.50	186.00	D034581	1.50		<0.005		0.001
185.70	186.20	FAI <b>Faille</b> zone de faille; pas possible de prendre un angle	186.00	187.50	D034582	1.50		<0.005		0.001
			187.50	189.00	D034583	1.50		<0.005		0.001
187.70	188.10	FAI <b>Faille</b> zone de faille; pas possible de prendre un angle	189.00	190.50	D034584	1.50		<0.005		0.001
			190.50	192.00	D034585	1.50		0.023		0.023
192.00	195.00	FAI <b>Faille</b> zone de faille; roche si fracturée que pas possible de prendre un angle;	192.00	193.50	D034586	1.50		<0.005		0.001
			193.50	195.00	D034587	1.50		<0.005		0.001
195.00	Fin du sondage Nombre d'échantillons : 125 Nombre d'échantillons QAQC : 17 Longueur totale échantillonnée : 184.60									



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.50	13.50	D034450	M	0.00	3.100	3.100
27.00	28.50	D034460	D034459	1.50	1.890	1.890
40.50	40.50	D034470	J	0.00	0.760	0.760
42.00	42.00	D034472	M1	0.00	<0.005	0.001
52.50	54.00	D034480	D034479	1.50	<0.005	0.001
66.00	66.00	D034490	K	0.00	1.130	1.130
79.50	81.00	D034500	D034499	1.50	<0.005	0.001
93.00	93.00	D034510	L	0.00	2.150	2.150
94.50	94.50	D034512	M1	0.00	<0.005	0.001
105.00	106.50	D034520	D034519	1.50	<0.005	0.001
118.50	118.50	D034530	M	0.00	3.380	3.380
132.00	133.50	D034540	D034539	1.50	<0.005	0.001
144.90	144.90	D034550	J	0.00	0.700	0.700
146.00	146.00	D034552	M1	0.00	<0.005	0.001
156.00	157.50	D034560	D034559	1.50	<0.005	0.001
169.50	169.50	D034570	K	0.00	1.190	1.190
183.00	184.50	D034580	D034579	1.50	0.010	0.010

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-204**

Titre minier :

Section :                      630900

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Myriam St-Louis

Lot :

Du :                      2010-05-03

Date de description :

Au :                      2010-05-03

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -70.00°  
 Longueur :                      105.00 m

Est	630 900.0
Nord	5 374 584.3
Élévation	282.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	358.30°	-68.20°	Oui
Reflex	9.00	4.60°	-68.10°	Non
Reflex	12.00	4.60°	-68.00°	Non
Reflex	15.00	4.30°	-68.00°	Non
Reflex	18.00	3.80°	-67.90°	Non
Reflex	21.00	3.70°	-67.90°	Non
Reflex	24.00	3.20°	-67.90°	Non
Reflex	27.00	2.90°	-67.80°	Non
Reflex	30.00	2.70°	-67.90°	Non
Reflex	33.00	2.50°	-67.90°	Non
Reflex	36.00	2.40°	-67.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	2.20°	-67.80°	Non
Reflex	42.00	2.20°	-67.80°	Non
Reflex	45.00	2.20°	-67.80°	Non
Reflex	48.00	2.10°	-67.80°	Non
Reflex	51.00	2.30°	-67.90°	Non
Reflex	54.00	2.20°	-67.90°	Non
Reflex	57.00	2.20°	-67.90°	Non
Reflex	60.00	2.20°	-67.90°	Non
Reflex	63.00	2.20°	-68.00°	Non
Reflex	66.00	2.10°	-68.00°	Non
Reflex	69.00	2.10°	-68.00°	Non
Reflex	72.00	2.10°	-68.10°	Non

Description

Erreurs dans la numérotation des blocs:

- 3m entre les blocs 42 et 43; 3m entre les blocs 43 et 45, 3m de trop (va de 42 à 43 à 45 au lieu de 42 à 45 à 48)
- 3m entre les blocs 93 et 99 (manque bloc 96), 3m en moins.

Les deux erreurs s'annulent.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Non

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	7.20	MT						
		<b>Mort-terrain</b>						
7.20	13.00	BA; MAS	7.20	8.50	D038001	1.30	0.006	0.006
		<b>Basalte; Roche massive</b>	8.50	10.00	D038002	1.50	<0.005	0.001
		Green basalt rich in leucoxene grains and chlorite, carbonaceous, pyrite found in some veins and rarely as euhedral crystals, epidote.	10.00	11.50	D038004	1.50	<0.005	0.001
			11.50	13.00	D038005	1.50	0.005	0.005
13.00	38.10	PR; MAS	13.00	14.50	D038006	1.50	<0.005	0.001
		<b>Pyroclastite grenue; Roche massive</b>	14.50	16.00	D038007	1.50	<0.005	0.001
		Medium grey tuff with a slightly greenish tinge, grading from fine to coarse grained (grading seen parallel to the core), occasional fine disseminated pyrite, some euhedral crystals and aggregates, some rounded grains, several dark grains that could be made of quartz, some carbonate grains and carbonates in hairs, veinlets and veins.	16.00	17.50	D038008	1.50	<0.005	0.001
			17.50	19.00	D038009	1.50	<0.005	0.001
			19.00	20.50	D038010	1.50	<0.005	0.001
			20.50	22.00	D038011	1.50	<0.005	0.001
			22.00	23.40	D038012	1.40	<0.005	0.001
			23.40	25.00	D038014	1.60	<0.005	0.001
			25.00	26.50	D038015	1.50	<0.005	0.001
			26.50	28.00	D038016	1.50	<0.005	0.001
			28.00	29.50	D038017	1.50	<0.005	0.001
			29.50	31.00	D038018	1.50	<0.005	0.001
			31.00	32.50	D038019	1.50	<0.005	0.001
			32.50	34.00	D038020	1.50	<0.005	0.001
			34.00	35.50	D038021	1.50	0.010	0.010
			35.50	37.00	D038022	1.50	<0.005	0.001
			37.00	38.10	D038024	1.10	<0.005	0.001
38.10	105.00	GA; MAS	38.10	39.00	D038025	0.90	<0.005	0.001
		<b>Gabbro; Roche massive</b>	39.00	40.50	D038026	1.50	<0.005	0.001
		Greyish-green gabbro, irregular contact with tuff, some pyrite aggregates, chlorite, carbonates, small feldspar grains, epidote, hematite in some areas.	40.50	42.00	D038027	1.50	<0.005	0.001
			42.00	43.50	D038028	1.50	<0.005	0.001
			43.50	45.00	D038029	1.50	<0.005	0.001
			45.00	46.50	D038031	1.50	<0.005	0.001
			46.50	48.00	D038032	1.50	<0.005	0.001
			48.00	49.50	D038034	1.50	<0.005	0.001
			49.50	51.00	D038035	1.50	<0.005	0.001
			51.00	52.50	D038036	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	52.50	54.00	D038037	1.50	<0.005		0.001
	54.00	55.50	D038038	1.50	<0.005		0.001
	55.50	57.00	D038039	1.50	<0.005		0.001
	57.00	58.50	D038040	1.50	<0.005		0.001
	58.50	60.00	D038041	1.50	<0.005		0.001
	60.00	61.50	D038042	1.50	<0.005		0.001
	61.50	63.00	D038044	1.50	<0.005		0.001
	63.00	64.50	D038045	1.50	<0.005		0.001
	64.50	66.00	D038046	1.50	<0.005		0.001
	66.00	67.50	D038047	1.50	<0.005		0.001
	67.50	69.00	D038048	1.50	0.005		0.005
	69.00	70.50	D038049	1.50	<0.005		0.001
	70.50	72.00	D038050	1.50	<0.005		0.001
	72.00	73.50	D038051	1.50	<0.005		0.001
	73.50	75.00	D038052	1.50	<0.005		0.001
	75.00	76.50	D038054	1.50	<0.005		0.001
	76.50	78.00	D038055	1.50	<0.005		0.001
	78.00	79.50	D038056	1.50	<0.005		0.001
	79.50	81.00	D038057	1.50	<0.005		0.001
	81.00	82.50	D038058	1.50	0.005		0.005
	82.50	84.00	D038059	1.50	<0.005		0.001
	84.00	85.50	D038060	1.50	<0.005		0.001
	85.50	87.00	D038061	1.50	<0.005		0.001
	87.00	88.50	D038062	1.50	<0.005		0.001
	88.50	90.00	D038064	1.50	<0.005		0.001
	90.00	91.50	D038065	1.50	<0.005		0.001
	91.50	93.00	D038066	1.50	<0.005		0.001
	93.00	94.50	D038067	1.50	<0.005		0.001
	94.50	96.00	D038068	1.50	<0.005		0.001
	96.00	97.50	D038069	1.50	<0.005		0.001
	97.50	99.00	D038071	1.50	<0.005		0.001
	99.00	100.50	D038072	1.50	<0.005		0.001
	100.50	102.00	D038074	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
38.10	70.50	CB <b>Carbonaté</b> Slightly to moderately calcified, carbonate grains and carbonates in hairs and veinlets, some less calcified areas.	102.00	103.50	D038075	1.50	<0.005		0.001
			103.50	105.00	D038076	1.50	<0.005		0.001
105.00	Fin du sondage Nombre d'échantillons : 66 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 97.80								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
8.50	10.00	D038003	D038002	1.50	<0.005	0.001
22.00	22.00	D038013	J	0.00	0.807	0.807
35.50	37.00	D038023	D038022	1.50	<0.005	0.001
43.50	43.50	D038030	M1	0.00	<0.005	0.001
46.50	46.50	D038033	K	0.00	1.015	1.015
60.00	61.50	D038043	D038042	1.50	<0.005	0.001
73.50	73.50	D038053	L	0.00	2.220	2.220
87.00	88.50	D038063	D038062	1.50	<0.005	0.001
96.00	96.00	D038070	M1	0.00	<0.005	0.001
99.00	99.00	D038073	M	0.00	3.180	3.180

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-205**

Titre minier :

Section :                      630900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Johan Bergé

Lot :

Du :                              2010-05-03

Date de description :

Au :                              2010-05-04

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      163.70 m

Est	630 900.5
Nord	5 374 510.6
Élévation	304.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	1.50°	-60.00°	Non
Reflex	8.00	1.80°	-59.90°	Non
Reflex	11.00	1.00°	-59.80°	Non
Reflex	14.00	0.80°	-59.90°	Non
Reflex	17.00	0.80°	-60.00°	Non
Reflex	20.00	0.80°	-60.00°	Non
Reflex	23.00	1.00°	-60.00°	Non
Reflex	26.00	1.20°	-60.00°	Non
Reflex	29.00	0.90°	-60.00°	Non
Reflex	32.00	1.00°	-60.10°	Non
Reflex	35.00	0.80°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.60°	-60.10°	Non
Reflex	41.00	0.50°	-60.10°	Non
Reflex	44.00	2.20°	-60.10°	Oui
Reflex	47.00	4.00°	-60.20°	Oui
Reflex	50.00	0.50°	-60.20°	Non
Reflex	53.00	1.40°	-60.20°	Non
Reflex	56.00	0.90°	-60.20°	Non
Reflex	59.00	1.20°	-60.30°	Non
Reflex	62.00	1.10°	-60.30°	Non
Reflex	65.00	2.70°	-60.30°	Non
Reflex	68.00	5.40°	-60.30°	Oui
Reflex	71.00	3.60°	-60.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.90	MT <b>Mort-terrain</b> No recovery.						
1.90	19.70	SY <b>Syénite</b> Syénite à grain moyen avec passage à feldspath centimétrique. L'altération est carbonatée en général, avec des passages non carbonatés hématisés (rouge), séricitisés (ocre) et chloritisés (verdâtre). Le réseau de veine/veinule/cheveux de quartz carbonate est très bien développé.	1.90	3.50	D031422	1.60	0.180	0.180
2.00	24.00	CH; HM <b>Chloriteux; Hématisé</b> Chloriteux et hématisé par endroit.	3.50	5.00	D031424	1.50	<0.005	0.001
			5.00	6.50	D031425	1.50	<0.005	0.001
			6.50	8.00	D031426	1.50	0.006	0.006
			8.00	9.50	D031427	1.50	0.006	0.006
			9.50	11.00	D031428	1.50	0.160	0.160
			11.00	12.50	D031429	1.50	0.086	0.086
			12.50	14.00	D031430	1.50	0.062	0.062
			14.00	15.50	D031431	1.50	0.082	0.082
			15.50	17.00	D031432	1.50	0.052	0.052
			17.00	18.50	D031434	1.50	0.077	0.077
			18.50	19.70	D031435	1.20	0.013	0.013
19.70	20.00	NR <b>Carotte perdue</b>						
20.00	163.70	SY <b>Syénite</b> Syénite à grain moyen avec passage à feldspath centimétrique. L'altération est carbonatée en général, avec des passages non carbonatés hématisés (rouge), séricitisés (ocre) et chloritisés (verdâtre). Le réseau de veine/veinule/cheveux de quartz carbonate est très bien développé. La minéralisation est généralement portée par des niveaux plus chloriteux qu'hématisés. L'unité est magnétique sur des zones métriques et des niveaux centimétriques.	20.00	21.50	D031436	1.50	0.518	0.518
			21.50	23.00	D031437	1.50	0.050	0.050
			23.00	24.50	D031438	1.50	<0.005	0.001
24.00	29.40	HM <b>Hématisé</b>	24.50	26.00	D031439	1.50	0.008	0.008



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			26.00	27.70	D031440	1.70	<0.005		0.001
			27.70	29.40	D031441	1.70	0.162		0.162
29.40	32.00	CH <b>Chloriteux</b>	29.40	31.10	D031442	1.70	0.047		0.047
			31.10	32.50	D031444	1.40	0.033		0.033
32.00	61.00	HM <b>Hématisé</b>	32.50	34.00	D031445	1.50	0.006		0.006
			34.00	35.50	D031446	1.50	<0.005		0.001
			35.50	37.00	D031447	1.50	0.007		0.007
			37.00	38.50	D031448	1.50	<0.005		0.001
			38.50	40.20	D031449	1.70	<0.005		0.001
			40.20	41.50	D031451	1.30	0.007		0.007
41.10	48.50	SY <b>Syénite</b> Syénite magnétique.	41.50	43.00	D031452	1.50	0.016		0.016
			43.00	44.50	D031454	1.50	<0.005		0.001
			44.50	46.00	D031455	1.50	<0.005		0.001
			46.00	47.50	D031456	1.50	<0.005		0.001
			47.50	49.00	D031457	1.50	0.040		0.040
			49.00	50.50	D031458	1.50	0.036		0.036
			50.50	52.00	D031459	1.50	0.049		0.049
			52.00	53.00	D031460	1.00	0.005		0.005
			53.00	54.50	D031461	1.50	0.776		0.776
			54.50	56.00	D031462	1.50	0.132		0.132
			56.00	57.50	D031464	1.50	0.175		0.175
			57.50	59.00	D031465	1.50	0.009		0.009
			59.00	60.50	D031466	1.50	0.036		0.036
			60.50	62.00	D031467	1.50	0.011		0.011
61.00	64.50	SR <b>Séricitique</b>	62.00	63.10	D031468	1.10	0.102		0.102
			63.10	64.50	D031469	1.40	0.110		0.110
63.40	64.80	FRC <b>Fracturé</b> Zone fracturée, broyée au milieu. Pas de carbonatation.							
64.50	156.20	HM <b>Hématisé</b>	64.50	65.70	D031470	1.20	0.043		0.043
64.80	78.20	SY <b>Syénite</b> Syénite magnétique.	65.70	67.00	D031471	1.30	1.890		1.890
			67.00	68.50	D031472	1.50	0.401		0.401
			68.50	70.00	D031474	1.50	0.192		0.192

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			70.00	71.50	D031475	1.50		0.212		0.212
			71.50	72.80	D031476	1.30		0.336		0.336
			72.80	74.50	D031477	1.70		0.015		0.015
			74.50	76.00	D031478	1.50		0.022		0.022
			76.00	76.90	D031479	0.90		1.875		1.875
			76.90	78.50	D031480	1.60		0.240		0.240
			78.50	80.00	D031481	1.50		0.016		0.016
			80.00	81.00	D031482	1.00		0.012		0.012
			81.00	82.20	D031484	1.20		0.013		0.013
			82.20	83.50	D031485	1.30		0.015		0.015
			83.50	85.00	D031486	1.50		0.011		0.011
			85.00	86.50	D031487	1.50		0.006		0.006
			86.50	88.00	D031488	1.50		0.008		0.008
87.50	88.00	QZVN	88.00	89.50	D031489	1.50		0.008		0.008
		<b>Veine de Quartz massive</b>	89.50	91.00	D031491	1.50		0.009		0.009
		Veine de quartz avec bréchification de la syénite encaissante	91.00	92.50	D031492	1.50		0.005		0.005
		accompagnée de chloritisation, surtout dans l'éponte supérieure	92.50	94.00	D031494	1.50		0.011		0.011
		(hanging wall).								
92.80	116.40	SY	94.00	95.50	D031495	1.50		0.006		0.006
		<b>Syénite</b>	95.50	97.00	D031496	1.50		0.006		0.006
		Syénite magnétique.	97.00	98.50	D031497	1.50		0.010		0.010
			98.50	100.00	D031498	1.50		0.028		0.028
			100.00	101.50	D031499	1.50		0.018		0.018
			101.50	103.00	D031500	1.50		0.010		0.010
			103.00	104.50	D031501	1.50		0.013		0.013
			104.50	106.00	D031502	1.50		0.069		0.069
			106.00	107.30	D031504	1.30		0.062		0.062
			107.30	109.00	D031505	1.70		<0.005		0.001
			109.00	110.50	D031506	1.50		<0.005		0.001
			110.50	112.00	D031507	1.50		0.091		0.091
			112.00	113.50	D031508	1.50		0.017		0.017
			113.50	115.00	D031509	1.50		0.171		0.171
			115.00	116.50	D031510	1.50		0.055		0.055
			116.50	118.00	D031511	1.50		0.339		0.339

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
128.20	140.00	SY Syénite	118.00	119.50	D031512	1.50	0.688		0.688
			119.50	121.00	D031514	1.50	0.024		0.024
			121.00	122.50	D031515	1.50	0.025		0.025
			122.50	124.00	D031516	1.50	0.007		0.007
			124.00	125.50	D031517	1.50	0.063		0.063
			125.50	127.00	D031518	1.50	0.074		0.074
			127.00	128.50	D031519	1.50	0.615		0.615
			128.50	129.90	D031520	1.40	0.489		0.489
			129.90	131.60	D031521	1.70	0.140		0.140
			131.60	133.00	D031522	1.40	0.377		0.377
			133.00	134.50	D031524	1.50	0.211		0.211
			134.50	136.00	D031525	1.50	0.128		0.128
			136.00	137.50	D031526	1.50	0.121		0.121
			137.50	139.00	D031527	1.50	0.213		0.213
			139.00	140.50	D031528	1.50	0.996		0.996
			140.50	142.00	D031529	1.50	0.180		0.180
			142.00	143.50	D031531	1.50	0.222		0.222
			143.50	145.00	D031532	1.50	0.287		0.287
			145.00	146.50	D031534	1.50	0.095		0.095
			146.50	147.50	D031535	1.00	0.791		0.791
147.50	148.70	D031536	1.20	0.150		0.150			
148.70	150.30	D031537	1.60	0.149		0.149			
150.30	152.00	D031538	1.70	0.135		0.135			
152.00	153.50	D031539	1.50	0.561		0.561			
153.50	155.00	D031540	1.50	0.146		0.146			
155.00	156.50	D031541	1.50	0.343		0.343			
156.20	158.80	CH Chloriteux	156.50	157.30	D031542	0.80	0.306	0.306	
			157.30	159.00	D031544	1.70	0.723	0.723	
158.80	163.70	HM Hématisé Hématisé et tendance chloritique à la fin du trou.	159.00	160.50	D031545	1.50	0.352	0.352	
			160.50	162.00	D031546	1.50	0.383	0.383	
			162.00	163.70	D031547	1.70	1.660	1.660	

# Corporation Minière Osisko Div. Exploration

163.70

Fin du sondage

Nombre d'échantillons : 110

Nombre d'échantillons QAQC : 16

Longueur totale échantillonnée : 161.50

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
1.90	3.50	D031423	D031422	1.60	0.133	0.133
15.50	15.50	D031433	K	0.00	1.060	1.060
29.40	31.10	D031443	D031442	1.70	0.048	0.048
38.50	38.50	D031450	M1	0.00	<0.005	0.001
41.50	41.50	D031453	L	0.00	2.020	2.020
54.50	56.00	D031463	D031462	1.50	0.112	0.112
67.00	67.00	D031473	M	0.00	3.070	3.070
80.00	81.00	D031483	D031482	1.00	0.007	0.007
88.00	88.00	D031490	M1	0.00	<0.005	0.001
91.00	91.00	D031493	J	0.00	0.747	0.747
104.50	106.00	D031503	D031502	1.50	0.063	0.063
118.00	118.00	D031513	K	0.00	0.999	0.999
131.60	133.00	D031523	D031522	1.40	0.357	0.357
140.50	140.50	D031530	M1	0.00	<0.005	0.001
143.50	143.50	D031533	L	0.00	2.280	2.280
156.50	157.30	D031543	D031542	0.80	0.330	0.330

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-206**

Titre minier :

Section :                      630800

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    A. Jean

Lot :

Du :                              2010-05-04

Date de description :        2010-06-30

Au :                              2010-05-05

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -62.00°  
 Longueur :                    240.00 m

Est	630 799.9
Nord	5 374 504.0
Élévation	311.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	6.00	1.90°	-61.60°	Non
Reflex	9.00	3.70°	-61.50°	Oui
Reflex	12.00	1.70°	-61.60°	Non
Reflex	15.00	1.00°	-61.60°	Non
Reflex	18.00	1.00°	-61.60°	Non
Reflex	21.00	0.90°	-61.80°	Non
Reflex	24.00	1.00°	-61.70°	Non
Reflex	27.00	1.10°	-61.60°	Non
Reflex	30.00	1.30°	-61.70°	Non
Reflex	33.00	1.00°	-61.60°	Non
Reflex	36.00	1.10°	-61.60°	Non
Reflex	39.00	1.00°	-61.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	42.00	1.20°	-61.70°	Non
Reflex	45.00	1.20°	-61.60°	Non
Reflex	48.00	1.30°	-61.70°	Non
Reflex	51.00	1.30°	-61.70°	Non
Reflex	54.00	1.40°	-61.80°	Non
Reflex	57.00	1.50°	-61.80°	Non
Reflex	60.00	1.50°	-61.70°	Non
Reflex	63.00	1.40°	-61.80°	Non
Reflex	66.00	1.40°	-61.70°	Non
Reflex	69.00	1.60°	-61.70°	Non
Reflex	72.00	3.10°	-61.80°	Oui
Reflex	75.00	1.80°	-61.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	142.70	SY; POR	0.00	1.50	D032261	1.50	0.005		0.005
		<b>Syénite; Porphyrique</b>	1.50	3.00	D032262	1.50	0.005		0.005
		Syénite à mésostase aphanitique avec des proportions variables de Po de Fp de 1 jusqu'à 10 mm, tantôt arrondis et prismatiques (à partir de 95m). La couleur de la syénite varie énormément, passant du rougeâtre au verdâtre, au vert fuschite et au rouge vin, et même au violacé. La syénite montre beaucoup de veinules de Qtz-Cb mm sans direction préférencielle mais le pendage 70°AC semble dominant.	3.00	4.50	D032264	1.50	<0.005		0.001
			4.50	6.00	D032265	1.50	<0.005		0.001
			6.00	7.50	D032266	1.50	0.005		0.005
			7.50	9.00	D032267	1.50	<0.005		0.001
			9.00	10.50	D032268	1.50	<0.005		0.001
		On observe une très faible quantité de Py extrêmement fine (à la loupe) alors que certains passages de syénite violacé montre de très petits xtaux brillants d'éclat métalliques qui pourraient être de L'arsénopyrite.	10.50	12.00	D032269	1.50	0.005		0.005
			12.00	13.50	D032270	1.50	0.024		0.024
			13.50	15.00	D032271	1.50	<0.005		0.001
			15.00	16.60	D032272	1.60	<0.005		0.001
		Le % de Sulfures semblent légèrement plus élevé dans la syénite verdâtre, variant de trace à 0,1%.							
0.00	16.60	HM20							
		<b>Hématisé 20</b>							
16.60	25.00	SR30							
		<b>Séricitique 30</b>							
		QQ Po altérés en fuschite. Cisaillement probable. Po allongés dans la schistosité avec des veinules de CB							
16.60	25.00	CIS	16.60	18.00	D032274	1.40	0.006		0.006
		<b>Cisaillement 25°</b>	18.00	19.00	D032275	1.00	<0.005		0.001
			19.00	20.00	D032276	1.00	<0.005		0.001
			20.00	21.50	D032277	1.50	0.016		0.016
			21.50	23.00	D032278	1.50	0.009		0.009
			23.00	24.00	D032279	1.00	0.055		0.055
			24.00	25.00	D032280	1.00	0.007		0.007
25.00	34.60	HM20	25.00	26.00	D032282	1.00	<0.005		0.001
		<b>Hématisé 20</b>	26.00	27.50	D032284	1.50	<0.005		0.001
			27.50	29.00	D032285	1.50	0.144		0.144
			29.00	30.50	D032286	1.50	0.008		0.008
			30.50	32.00	D032287	1.50	0.006		0.006
			32.00	33.50	D032288	1.50	0.008		0.008
			33.50	34.60	D032289	1.10	<0.005		0.001
34.60	41.20	SR30							

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Séricitique 30</b> QQ Po altérés en fuschite. Cisaillement probable à 30°AC. Po allongés dans la schistosité avec des veinules de CB						
34.60	41.20	CIS	34.60	35.50	D032290	0.90	<0.005	0.001
		<b>Cisaillement 40°</b>	35.50	36.50	D032291	1.00	<0.005	0.001
			36.50	38.00	D032292	1.50	0.009	0.009
			38.00	39.50	D032294	1.50	0.020	0.020
			39.50	41.20	D032295	1.70	0.011	0.011
41.20	56.60	HM30	41.20	42.50	D032296	1.30	<0.005	0.001
		<b>Hématisé 30</b>	42.50	44.00	D032297	1.50	<0.005	0.001
			44.00	45.50	D032298	1.50	<0.005	0.001
			45.50	47.00	D032299	1.50	<0.005	0.001
			47.00	48.50	D032300	1.50	<0.005	0.001
			48.50	50.00	D032301	1.50	<0.005	0.001
			50.00	51.50	D032302	1.50	<0.005	0.001
			51.50	53.00	D032304	1.50	<0.005	0.001
			53.00	54.50	D032305	1.50	<0.005	0.001
			54.50	55.50	D032306	1.00	<0.005	0.001
			55.50	56.60	D032307	1.10	<0.005	0.001
56.60	62.70	SR20						
		<b>Séricitique 20</b> Cisaillement probable. Po allongés dans la schistosité avec des veinules de CB						
56.60	62.70	CIS	56.60	57.50	D032308	0.90	0.018	0.018
		<b>Cisaillement 35°</b>	57.50	59.00	D032309	1.50	0.099	0.099
			59.00	60.50	D032310	1.50	0.006	0.006
			60.50	61.60	D032311	1.10	<0.005	0.001
			61.60	62.70	D032312	1.10	0.005	0.005
62.70	68.20	HM20	62.70	63.50	D032314	0.80	<0.005	0.001
		<b>Hématisé 20</b>	63.50	65.00	D032315	1.50	<0.005	0.001
			65.00	66.50	D032316	1.50	<0.005	0.001
			66.50	68.20	D032317	1.70	<0.005	0.001
68.20	68.80	SR30						
		<b>Séricitique 30</b> Cisaillement net à 30°AC.						



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
68.20	68.80	CIS <b>Cisaillement 40°</b>	68.20	68.80	D032318	0.60	<0.005		0.001
68.80	83.20	HM30 <b>Hématisé 30</b> Beaucoup de veinules de Cb-Qtz	68.80	69.50	D032319	0.70	<0.005		0.001
			69.50	71.00	D032320	1.50	<0.005		0.001
			71.00	72.50	D032322	1.50	<0.005		0.001
			72.50	74.00	D032324	1.50	0.012		0.012
			74.00	75.50	D032325	1.50	0.011		0.011
			75.50	77.00	D032326	1.50	0.162		0.162
			77.00	78.50	D032327	1.50	<0.005		0.001
			78.50	80.00	D032328	1.50	<0.005		0.001
			80.00	81.50	D032329	1.50	<0.005		0.001
			81.50	83.20	D032330	1.70	<0.005		0.001
83.20	84.10	SR60 <b>Séricitique 60</b> Cisaillement intense à 80°AC avec inj. de Qtz irr.. Vert fuschite							
83.20	84.10	CIS <b>Cisaillement 80°</b>	83.20	84.10	D032331	0.90	0.039		0.039
84.10	87.90	HM25 <b>Hématisé 25</b>	84.10	85.60	D032332	1.50	<0.005		0.001
			85.60	86.90	D032334	1.30	<0.005		0.001
			86.90	88.20	D032335	1.30	0.018		0.018
87.90	88.20	SR30 <b>Séricitique 30</b> Cisaillement évident à 45°AC, forte séricitisation avec fuschite et injecté de 2 veines de Qtz-Cb à 45°ac de 3 cm d"ép.							
87.90	88.20	CIS <b>Cisaillement 45°</b>							
88.20	94.50	HM30 <b>Hématisé 30</b> Beaucoup de veinules de CB à 20° AC.	88.20	89.00	D032336	0.80	0.083		0.083
			89.00	90.50	D032337	1.50	0.117		0.117
			90.50	92.00	D032338	1.50	<0.005		0.001
			92.00	93.50	D032339	1.50	0.007		0.007
			93.50	94.50	D032340	1.00	0.010		0.010
94.50	97.30	SI50; SR20 <b>Silicifié 50; Séricitique 20</b> Zone perturbée avec remplacement par la silice. Séricitisation pervasive montrant qq Po fuschitisés. Le % de Py est + élevé, env. 0.5%							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
94.50	97.30	CAT	94.50	96.00	D032341	1.50	0.079		0.079
		<b>Cataclasé</b>	96.00	97.30	D032342	1.30	0.048		0.048
97.30	143.60	HM50	97.30	98.00	D032344	0.70	0.007		0.007
		<b>Hématisé 50</b>	98.00	99.50	D032345	1.50	<0.005		0.001
		Couleur violacée à sanguin.	99.50	101.00	D032346	1.50	<0.005		0.001
			101.00	102.50	D032347	1.50	0.017		0.017
			102.50	104.00	D032348	1.50	<0.005		0.001
			104.00	105.50	D032349	1.50	<0.005		0.001
			105.50	107.00	D032350	1.50	<0.005		0.001
			107.00	108.50	D032351	1.50	0.077		0.077
			108.50	110.00	D032352	1.50	<0.005		0.001
			110.00	111.50	D032354	1.50	<0.005		0.001
			111.50	113.00	D032355	1.50	0.011		0.011
			113.00	114.50	D032356	1.50	0.005		0.005
			114.50	116.00	D032357	1.50	<0.005		0.001
			116.00	117.50	D032358	1.50	<0.005		0.001
117.00	122.40	FRC	117.50	119.00	D032359	1.50	<0.005		0.001
		<b>Fracturé</b>	119.00	120.50	D032360	1.50	<0.005		0.001
			120.50	122.00	D032362	1.50	<0.005		0.001
			122.00	123.50	D032364	1.50	0.021		0.021
			123.50	125.00	D032365	1.50	0.067		0.067
			125.00	126.50	D032366	1.50	0.185		0.185
			126.50	128.00	D032367	1.50	0.008		0.008
			128.00	129.50	D032368	1.50	0.014		0.014
			129.50	131.00	D032369	1.50	0.048		0.048
			131.00	132.50	D032370	1.50	0.019		0.019
			132.50	134.00	D032371	1.50	0.006		0.006
			134.00	135.50	D032372	1.50	0.028		0.028
	135.50	137.00	D032374	1.50	0.010		0.010		
	137.00	138.50	D032375	1.50	0.088		0.088		
	138.50	140.00	D032376	1.50	0.006		0.006		
	140.00	141.20	D032377	1.20	<0.005		0.001		
	141.20	142.40	D032378	1.20	0.009		0.009		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
142.70	239.99	SY <b>Syénite</b> Graduellement, la syénite porphyrique passe à une syénite massive, rougeâtre/rouge vin/sanguine avec absence presque total de Po de Fp.  Fin du trou dans une ouverture minière à 240 m .  Veine de calcite massive de 235.5 à 237.8, juste après la boue de faille (234.4 à 234.5)	142.40	143.60	D032379	1.20	0.014		0.014
143.60	144.50	SR30 <b>Séricitique 30</b>							
143.60	144.50	CIS <b>Cisaillement 10°</b> Séricitisée avec 0.5% Py	143.60	144.50	D032380	0.90	0.069		0.069
144.50	149.30	HM30 <b>Hématisé 30</b>	144.50	146.00	D032381	1.50	0.028		0.028
			146.00	147.60	D032382	1.60	0.005		0.005
			147.60	149.30	D032384	1.70	0.050		0.050
149.30	150.00	SR40 <b>Séricitique 40</b>							
149.30	150.00	CIS <b>Cisaillement 45°</b> Séricitisée avec filons de qtz à 85°AC stérile	149.30	150.70	D032385	1.40	0.164		0.164
150.00	152.60	HM30 <b>Hématisé 30</b>	151.70	153.40	D032386	1.70	0.158		0.158
152.60	153.40	SR40 <b>Séricitique 40</b>							
152.60	153.40	CIS <b>Cisaillement 5°</b> Séricitisée							
153.40	164.70	HM40 <b>Hématisé 40</b>	153.40	155.00	D032387	1.60	0.026		0.026
			155.00	156.50	D032388	1.50	<0.005		0.001
			156.50	158.00	D032389	1.50	0.023		0.023
			158.00	159.50	D032390	1.50	0.087		0.087
			159.50	161.00	D032391	1.50	<0.005		0.001
			161.00	162.50	D032392	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			162.50	164.00	D032394	1.50	<0.005		0.001
			164.00	165.50	D032395	1.50	0.306		0.306
164.70	165.50	SR25 <b>Séricitique 25</b>							
164.70	165.50	CIS <b>Cisaillement 15°</b>							
		Fortement séricitisée, avec filon de qtz irr // AC							
165.50	218.00	HM35 <b>Hématisé 35</b>	165.50	167.00	D032396	1.50	0.150		0.150
			167.00	168.50	D032397	1.50	0.423		0.423
			168.50	170.00	D032398	1.50	<0.005		0.001
			170.00	171.50	D032399	1.50	<0.005		0.001
			171.50	173.00	D032400	1.50	0.005		0.005
			173.00	174.50	D032402	1.50	0.005		0.005
			174.50	176.00	D032404	1.50	0.011		0.011
			176.00	177.50	D032405	1.50	0.030		0.030
			177.50	179.00	D032406	1.50	0.011		0.011
			179.00	180.50	D032407	1.50	0.020		0.020
			180.50	182.00	D032408	1.50	0.743		0.743
			182.00	183.50	D032409	1.50	0.020		0.020
			183.50	185.00	D032410	1.50	0.059		0.059
			185.00	186.50	D032411	1.50	<0.005		0.001
			186.50	188.00	D032412	1.50	0.033		0.033
			188.00	189.50	D032414	1.50	0.016		0.016
			189.50	191.00	D032415	1.50	0.626		0.626
			191.00	192.50	D032416	1.50	1.350		1.350
			192.50	194.00	D032417	1.50	0.153		0.153
			194.00	195.50	D032418	1.50	0.010		0.010
			195.50	197.00	D032419	1.50	0.007		0.007
			197.00	198.50	D032420	1.50	0.008		0.008
			198.50	200.00	D032421	1.50	0.007		0.007
			200.00	201.50	D032422	1.50	<0.005		0.001
			201.50	203.00	D032424	1.50	<0.005		0.001
			203.00	204.50	D032425	1.50	<0.005		0.001
			204.50	206.00	D032426	1.50	0.021		0.021

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			206.00	207.50	D032427	1.50		0.330		0.330
			207.50	209.00	D032428	1.50		0.173		0.173
			209.00	210.50	D032429	1.50		0.660		0.660
			210.50	212.00	D032430	1.50		0.759		0.759
			212.00	213.50	D032431	1.50		0.012		0.012
			213.50	215.00	D032432	1.50		0.020		0.020
			215.00	216.50	D032434	1.50		0.005		0.005
			216.50	218.00	D032435	1.50		0.010		0.010
218.00	219.00	SR30 <b>Séricitique 30</b>								
218.00	219.00	CIS <b>Cisaillement 10°</b> Fortement séricitisée avec filons/amas de qtz-cb irr. + ou- // AC.	218.00	219.00	D032436	1.00		0.011		0.011
219.00	223.60	HM30 <b>Hématisé 30</b>	219.00	220.00	D032437	1.00		0.042		0.042
			220.00	221.00	D032438	1.00		0.014		0.014
			221.00	222.50	D032439	1.50		0.029		0.029
			222.50	224.00	D032440	1.50		0.343		0.343
223.60	240.00	CB40; HM20 <b>Carbonaté 40; Hématisé 20</b>	224.00	225.50	D032442	1.50		0.073		0.073
			225.50	227.00	D032444	1.50		0.021		0.021
			227.00	228.50	D032445	1.50		0.052		0.052
			228.50	230.00	D032446	1.50		0.075		0.075
			230.00	231.50	D032447	1.50		0.011		0.011
			231.50	233.00	D032448	1.50		0.033		0.033
			233.00	234.50	D032449	1.50		0.012		0.012
			234.50	236.00	D032450	1.50		0.012		0.012
			236.00	237.50	D032451	1.50		0.007		0.007
237.40	237.50	FAI <b>Faïlle</b> Boue de faille	237.50	239.00	D032452	1.50		1.420		1.420
			239.00	240.00	D032454	1.00		0.008		0.008
239.99	240.00	OM <b>Ouverture minière</b>								
240.00	<b>Fin du sondage</b> Nombre d'échantillons : 169 Nombre d'échantillons QAQC : 25 Longueur totale échantillonnée : 239.00									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
1.50	1.50	D032263	L	0.00	2.200	2.200
15.00	16.60	D032273	D032272	1.60	<0.005	0.001
24.00	24.00	D032281	M1	0.00	<0.005	0.001
25.00	25.00	D032283	M	0.00	3.220	3.220
36.50	38.00	D032293	D032292	1.50	0.005	0.005
50.00	50.00	D032303	J	0.00	0.804	0.804
61.60	62.70	D032313	D032312	1.10	<0.005	0.001
69.50	69.50	D032321	M1	0.00	<0.005	0.001
71.00	71.00	D032323	K	0.00	1.155	1.155
84.10	85.60	D032333	D032332	1.50	0.006	0.006
96.00	96.00	D032343	J	0.00	0.722	0.722
108.50	110.00	D032353	D032352	1.50	<0.005	0.001
119.00	119.00	D032361	M1	0.00	<0.005	0.001
120.50	120.50	D032363	M	0.00	2.840	2.840
134.00	135.50	D032373	D032372	1.50	0.028	0.028
146.00	146.00	D032383	J	0.00	0.724	0.724
161.00	162.50	D032393	D032392	1.50	<0.005	0.001
171.50	171.50	D032401	M1	0.00	<0.005	0.001
173.00	173.00	D032403	K	0.00	1.055	1.055
186.50	188.00	D032413	D032412	1.50	0.035	0.035
200.00	200.00	D032423	L	0.00	2.260	2.260
213.50	215.00	D032433	D032432	1.50	<0.005	0.001
222.50	222.50	D032441	M1	0.00	<0.005	0.001
224.00	224.00	D032443	M	0.00	3.000	3.000
237.50	239.00	D032453	D032452	1.50	0.175	0.175

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-207**

Titre minier :

Section :                      631000

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      S. Savadogo

Lot :

Du :                              2010-05-06

Date de description :              2010-06-21

Au :                              2010-05-07

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -58.00°  
 Longueur :                      165.60 m

Est	630 999.9
Nord	5 374 440.6
Élévation	308.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	0.00°	0.00°	Oui
Reflex	8.00	1.00°	-58.10°	Non
Reflex	11.00	0.10°	-58.30°	Non
Reflex	14.00	0.20°	-57.80°	Non
Reflex	17.00	0.00°	-57.80°	Non
Reflex	20.00	0.50°	-57.50°	Non
Reflex	23.00	0.20°	-56.80°	Non
Reflex	26.00	359.50°	-56.30°	Non
Reflex	29.00	0.10°	-56.60°	Non
Reflex	32.00	359.90°	-56.50°	Non
Reflex	35.00	0.10°	-56.60°	Non
Reflex	38.00	1.60°	-56.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	41.00	1.40°	-57.00°	Non
Reflex	44.00	0.40°	-56.80°	Non
Reflex	47.00	0.80°	-56.60°	Non
Reflex	50.00	1.10°	-56.60°	Non
Reflex	53.00	1.70°	-56.60°	Non
Reflex	56.00	2.90°	-56.70°	Oui
Reflex	59.00	1.90°	-56.70°	Non
Reflex	62.00	4.20°	-56.80°	Oui
Reflex	65.00	3.00°	-56.70°	Non
Reflex	68.00	1.20°	-56.80°	Non
Reflex	71.00	2.30°	-56.80°	Non
Reflex	74.00	3.30°	-57.10°	Non

Description

Erreur de metrage de la part des foreur: 2blocs de 65m;

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.50	MT <b>Mort-terrain</b> MT							
2.50	11.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique avec des phénocristaux de quartz-chlorite; plus ou moins carbonaté, peu chloritisé et modérément hématisé; peu à plus ou moins magnétisé; zone fractué et lessivée par l'eau; cristaux de pyrite disséminé jusqu'à 0,2%; contact graduels;							
2.50	17.00	HM03; CB03; CH02 <b>Hématisé 3; Carbonaté 3; Chloriteux 2</b> plus ou moins carbonaté; peu chloriteux; plus ou moins hématisé; zone lessivée par l'eau de surface;	2.50	4.00	D034322	1.50	<0.005		0.001
			4.00	5.00	D034323	1.00	<0.005		0.001
			5.00	6.50	D034324	1.50	<0.005		0.001
			6.50	8.00	D034325	1.50	0.267		0.267
			8.00	9.50	D034326	1.50	0.643		0.643
			9.50	11.00	D034327	1.50	0.029		0.029
11.00	11.80	NR <b>Carotte perdue</b> NR							
11.80	15.20	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique avec des phénocristaux de quartz-chlorite; plus ou moins carbonaté, peu chloritisé et modérément hématisé; peu à plus ou moins magnétisé; zone fractué et lessivée par l'eau; cristaux de pyrite disséminé jusqu'à 0,2%;	11.80	13.00	D034328	1.20	0.033		0.033
			13.00	14.00	D034329	1.00	0.005		0.005
			14.00	15.20	D034331	1.20	<0.005		0.001
15.20	15.70	NR <b>Carotte perdue</b> NR.							
15.70	17.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique avec des phénocristaux de quartz-chlorite; plus ou moins carbonaté, peu chloritisé et modérément hématisé; peu à plus ou moins magnétisé; zone fractué et lessivée par l'eau; cristaux de pyrite disséminé jusqu'à 0,2%;	15.70	16.60	D034332	0.90	<0.005		0.001
			16.80	18.50	D034333	1.70	0.005		0.005
17.00	23.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique avec des phénocristaux de quartz-calcite peu chloriteux; altéré plus ou moins à la chlorite et plus ou moins au carbonate; peu à plus ou moins magnétisé; zone partiellement lessivée par l'eau; cristaux de pyrite disséminé jusqu'à 0,2%; contenant un							



Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
17.00	23.00	CH03 <b>Chloriteux 3</b> plus ou moins chloriteux;	18.50	20.00	D034334	1.50	0.010	0.010			
			20.00	21.50	D034335	1.50	0.061	0.061			
			21.50	23.00	D034336	1.50	0.009	0.009			
23.00	40.80	SY; POR <b>Syénite 50°; Porphyrique</b> syénite porphyrique avec des phénocristaux de quartz-calcite peu chloriteux; altéré plus ou moins au carbonate et modérément hématisé; peu à plus ou moins magnétisé; cristaux de pyrite disséminé jusqu'à 0,2%; contenant un passage chloriteux entre 29,6m et 30m; contacts graduels;	23.00	24.50	D034337	1.50	<0.005	0.001			
			24.50	26.00	D034338	1.50	<0.005	0.001			
			26.00	27.50	D034339	1.50	<0.005	0.001			
			27.50	29.00	D034341	1.50	<0.005	0.001			
			29.00	30.50	D034342	1.50	0.005	0.005			
			30.50	32.00	D034343	1.50	0.013	0.013			
			32.00	33.50	D034344	1.50	<0.005	0.001			
			33.50	35.00	D034345	1.50	<0.005	0.001			
			35.00	36.50	D034346	1.50	<0.005	0.001			
			36.50	38.00	D034347	1.50	0.006	0.006			
			38.00	39.50	D034348	1.50	0.473	0.473			
			39.50	41.00	D034349	1.50	0.314	0.314			
			40.80	47.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite peu porphyrique avec des phénocristaux de quartz-calcite peu chloriteux; altéré plus ou moins à modérément à la chlorite et plus ou moins au carbonate; peu à plus ou moins magnétisé; cristaux de pyrite disséminé jusqu'à 0,2%; contenant des passages lessivés par l'eau;	41.00	42.50	D034351	1.50	0.035	0.035
						42.50	44.00	D034353	1.50	0.046	0.046
44.00	45.50	D034354				1.50	0.421	0.421			
45.50	47.00	D034355				1.50	0.789	0.789			
47.00	165.60	D034356				1.50	<0.005	0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
<b>Syénite 45°; Porphyrique</b>			48.50	50.00	D034357	1.50	<0.005	0.001
syénite porphyrique avec des phénocristaux de quartz-calcite peu chloriteux-hématisé et grossiers; modérément hématisé et plus ou moins carbonaté; peu à plus ou moins magnétisé; contient une zone lessivée par l'eau entre 68m et 70m; cristaux de pyrite disséminé jusqu'à 0,2%;			50.00	51.50	D034358	1.50	<0.005	0.001
			51.50	53.00	D034359	1.50	<0.005	0.001
			53.00	54.50	D034361	1.50	0.008	0.008
			54.50	56.00	D034362	1.50	<0.005	0.001
contenant des zones chloriteuses (119m-123.5m), une zone de brèche (130.8m-132.5m);			56.00	57.50	D034363	1.50	<0.005	0.001
			57.50	59.00	D034364	1.50	<0.005	0.001
			59.00	60.50	D034365	1.50	<0.005	0.001
			60.50	62.00	D034366	1.50	<0.005	0.001
			62.00	63.50	D034367	1.50	<0.005	0.001
			63.50	65.00	D034368	1.50	0.009	0.009
			65.00	66.50	D034369	1.50	0.059	0.059
			66.50	68.00	D034371	1.50	0.009	0.009
			68.00	69.50	D034372	1.50	0.006	0.006
			69.50	71.00	D034373	1.50	<0.005	0.001
			71.00	72.50	D034374	1.50	<0.005	0.001
			72.50	74.00	D034375	1.50	<0.005	0.001
			74.00	75.50	D034376	1.50	<0.005	0.001
			75.50	77.00	D034377	1.50	<0.005	0.001
47.00	77.00	HM05; CB03; CH02						
<b>Hématisé 5; Carbonaté 3; Chloriteux 2</b>								
modérément hématisé; plus ou moins carbonaté; peu chloriteux;								
77.00	83.00	CB03; HM03; CH02; SR02	77.00	78.50	D034378	1.50	0.040	0.040
<b>Carbonaté 3; Hématisé 3; Chloriteux 2; Séricitique 2</b>			78.50	80.00	D034379	1.50	0.005	0.005
plus ou moins carbonaté, plus ou moins hématisé, peu chloriteux, peu sericitisé;			80.00	81.50	D034381	1.50	0.217	0.217
			81.50	83.00	D034382	1.50	0.009	0.009
83.00	90.50	HM03; CB03; SR02	83.00	84.50	D034383	1.50	0.080	0.080
<b>Hématisé 3; Carbonaté 3; Séricitique 2</b>			84.50	86.00	D034384	1.50	0.066	0.066
plus ou moins hématisé, plus ou moins carbonaté, peu sericitisé (entre 83m et 84,5m);			86.00	87.50	D034385	1.50	0.007	0.007
			87.50	89.00	D034386	1.50	0.041	0.041
			89.00	90.50	D034387	1.50	0.011	0.011
90.50	119.00	HM05; CB03	90.50	92.00	D034388	1.50	0.007	0.007
<b>Hématisé 5; Carbonaté 3</b>			92.00	93.50	D034389	1.50	<0.005	0.001
modérément hématisé, plus ou moins carbonaté;			93.50	95.00	D034391	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			95.00	96.50	D034393	1.50	<0.005		0.001
			96.50	98.00	D034394	1.50	<0.005		0.001
			98.00	99.50	D034395	1.50	<0.005		0.001
			99.50	101.00	D034396	1.50	<0.005		0.001
			101.00	102.50	D034397	1.50	<0.005		0.001
			102.50	104.00	D034398	1.50	0.065		0.065
			104.00	105.50	D034399	1.50	0.005		0.005
			105.50	107.00	D034401	1.50	0.008		0.008
			107.00	108.50	D034402	1.50	<0.005		0.001
			108.50	110.00	D034403	1.50	0.014		0.014
			110.00	111.50	D034404	1.50	0.029		0.029
			111.50	113.00	D034405	1.50	0.024		0.024
			113.00	114.50	D034406	1.50	1.040		1.040
			114.50	116.00	D034407	1.50	0.165		0.165
			116.00	117.50	D034408	1.50	<0.005		0.001
			117.50	119.00	D034409	1.50	0.022		0.022
119.00	123.50	CH03; CB03; HM02	119.00	120.50	D034411	1.50	0.139		0.139
		<b>Chloriteux 3; Carbonaté 3; Hématisé 2</b>	120.50	122.00	D034412	1.50	0.276		0.276
		plus ou moins chloriteux; plus ou moins carbonaté;	122.00	123.50	D034413	1.50	0.430		0.430
123.50	147.00	HM05; CB03	123.50	125.00	D034414	1.50	0.006		0.006
		<b>Hématisé 5; Carbonaté 3</b>	125.00	126.50	D034415	1.50	0.007		0.007
		modérément hématisé; plus ou moins carbonaté;	126.50	128.00	D034416	1.50	0.017		0.017
			128.00	129.50	D034417	1.50	0.039		0.039
			129.50	131.00	D034418	1.50	0.167		0.167
			131.00	132.50	D034419	1.50	0.114		0.114
			132.50	134.00	D034421	1.50	0.104		0.104
			134.00	135.50	D034422	1.50	0.080		0.080
			135.50	137.00	D034423	1.50	0.296		0.296
			137.00	138.50	D034424	1.50	0.185		0.185
			138.50	140.00	D034425	1.50	0.152		0.152
			140.00	141.50	D034426	1.50	0.022		0.022
			141.50	143.00	D034427	1.50	0.011		0.011
			143.00	144.50	D034428	1.50	0.516		0.516

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
147.00	165.60	CH03; CB03; HM02; SR03 <b>Chloriteux 3; Carbonaté 3; Hématisé 2; Séricitique 3</b> plus ou moins chloriteux; plus ou moins carbonaté; peu hématisé; et plus ou moins sericitisé à partir de 162m	144.50	146.00	D034429	1.50	0.378		0.378
			146.00	147.50	D034431	1.50	0.118		0.118
			147.50	149.00	D034433	1.50	0.796		0.796
			149.00	150.50	D034434	1.50	0.041		0.041
			150.50	152.00	D034435	1.50	0.042		0.042
			152.00	153.50	D034436	1.50	0.032		0.032
			153.50	155.00	D034437	1.50	0.084		0.084
			155.00	156.50	D034438	1.50	0.052		0.052
			156.50	158.00	D034439	1.50	0.109		0.109
			158.00	159.50	D034441	1.50	0.025		0.025
			159.50	161.00	D034442	1.50	0.207		0.207
			161.00	162.50	D034443	1.50	0.418		0.418
			162.00	165.60	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée jusqu'à 0,5%;	162.50	164.00	D034444	1.50
164.00	165.60	D034445				1.60	1.355		1.355
165.60	Fin du sondage Nombre d'échantillons : 109 Nombre d'échantillons QAQC : 15 Longueur totale échantillonnée : 161.60								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.00	13.00	D034330	K	0.00	1.105	1.105
26.00	27.50	D034340	D034339	1.50	<0.005	0.001
39.50	39.50	D034350	L	0.00	2.090	2.090
41.00	41.00	D034352	M1	0.00	<0.005	0.001
51.50	53.00	D034360	D034359	1.50	<0.005	0.001
65.00	65.00	D034370	M	0.00	3.320	3.320
78.50	80.00	D034380	D034379	1.50	<0.005	0.001
92.00	92.00	D034390	J	0.00	0.755	0.755
93.50	93.50	D034392	M1	0.00	<0.005	0.001
104.00	105.50	D034400	D034399	1.50	0.005	0.005
117.50	117.50	D034410	K	0.00	0.948	0.948
131.00	132.50	D034420	D034419	1.50	0.111	0.111
144.50	144.50	D034430	L	0.00	2.160	2.160
146.00	146.00	D034432	M1	0.00	<0.005	0.001
156.50	158.00	D034440	D034439	1.50	0.166	0.166

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-208**

Titre minier :

Section :                      630200

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Myriam St-Louis/Johan  
Bergé

Lot :

Du :                      2010-05-03

Date de description :

Au :                      2010-05-04

Collet

UTM

Azimut :                      0.00°  
Plongée :                      -45.00°  
Longueur :                      61.00 m

Est	630 200.0
Nord	5 374 497.2
Élévation	287.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	5.00	0.00°	0.00°	Oui
Reflex	8.00	340.30°	-43.90°	Oui
Reflex	11.00	349.10°	-43.80°	Oui
Reflex	14.00	352.60°	-43.90°	Oui
Reflex	17.00	358.50°	-43.90°	Non
Reflex	20.00	360.00°	-43.90°	Non
Reflex	23.00	0.20°	-43.90°	Non
Reflex	26.00	0.40°	-44.00°	Non
Reflex	29.00	0.60°	-44.00°	Non
Reflex	32.00	0.50°	-44.00°	Non
Reflex	35.00	0.60°	-44.10°	Non
Reflex	38.00	0.30°	-44.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	41.00	0.80°	-44.10°	Non
Reflex	44.00	0.90°	-44.20°	Non
Reflex	47.00	0.90°	-44.20°	Non
Reflex	50.00	0.70°	-44.20°	Non
Reflex	53.00	0.70°	-44.20°	Non
Reflex	56.00	0.70°	-44.20°	Non
Reflex	59.00	0.20°	-44.30°	Non
Reflex	60.50	1.10°	-44.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	15.00	MT <b>Mort-terrain</b> Pas de carotte							
15.00	60.40	SY <b>Syénite</b> Syénite avec altération variée (hématite, carbonates, chlorite, silice, séricite), phénocristaux souvent zonés et parfois complètement remplacés (hématite, chlorite, séricite), plusieurs sont isométriques et d'autres ont les bords arrondis. Début fortement hématisé et magnétique. Fine pyrite disséminée à quelques endroits. Zone avec phénocristaux uniquement avec altération hématitique, absence quand chloritisée.	15.00	16.50	D038661	1.50	0.020		0.020
			16.50	18.00	D038662	1.50	0.014		0.014
			18.00	19.50	D038664	1.50	0.026		0.026
			19.50	21.00	D038665	1.50	<0.005		0.001
			21.00	22.50	D038666	1.50	0.025		0.025
			22.50	23.50	D038667	1.00	0.005		0.005
			23.50	24.40	D038668	0.90	0.007		0.007
			24.40	26.00	D038669	1.60	1.665		1.665
			26.00	27.20	D038671	1.20	0.893		0.893
			27.20	28.10	D038672	0.90	0.085		0.085
			28.10	29.50	D038674	1.40	0.113		0.113
			29.50	31.00	D038675	1.50	0.247		0.247
			31.00	32.00	D038676	1.00	0.387		0.387
			32.00	33.00	D038677	1.00	1.120		1.120
			33.00	34.40	D038678	1.40	0.334		0.334
			34.40	36.00	D038679	1.60	0.064		0.064
			36.00	37.50	D038680	1.50	0.139		0.139
			37.50	39.00	D038681	1.50	0.091		0.091
			39.00	40.50	D038682	1.50	0.200		0.200
			40.50	42.00	D038684	1.50	0.150		0.150
			42.00	43.50	D038685	1.50	0.258		0.258
			43.50	45.00	D038686	1.50	0.098		0.098
15.00	45.00	CB; HM <b>Carbonaté; Hématisé</b> Syénite rose-verdâtre modérément carbonatée et hématisée, légèrement chloritisée par endroits.							
45.00	60.40	CB; CH; SI <b>Carbonaté; Chloriteux; Silicifié</b> Syénite verdâtre carbonatée et chloritisée. Séricité par endroits, et passages silicifiés décimétriques.	45.00	46.60	D038687	1.60	0.069		0.069
			46.60	48.00	D038688	1.40	0.142		0.142
			48.00	49.50	D038689	1.50	0.287		0.287
			49.50	51.00	D038690	1.50	0.141		0.141
			51.00	52.50	D038691	1.50	0.169		0.169

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
60.40	61.00	NR <b>Carotte perdue</b> Fin d'échantillon manquant (boue de forage).	52.50	54.00	D038692	1.50	1.525		1.525
			54.00	55.00	D038694	1.00	3.310		3.310
			55.00	56.00	D038695	1.00	5.170		5.170
			56.00	57.50	D038696	1.50	5.620		5.620
			57.50	59.00	D038697	1.50	4.650		4.650
			59.00	60.40	D038698	1.40	8.800		8.800
61.00	Fin du sondage Nombre d'échantillons : 33 Nombre d'échantillons QAQC : 5 Longueur totale échantillonnée : 45.40								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
16.50	18.00	D038663	D038662	1.50	0.018	0.018
24.40	24.40	D038670	M1	0.00	<0.005	0.001
27.20	27.20	D038673	K	0.00	1.035	1.035
39.00	40.50	D038683	D038682	1.50	0.189	0.189
52.50	52.50	D038693	L	0.00	2.090	2.090

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-209**

Titre minier :

Section :                      630200

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    David RUHARA

Lot :

Du :                              2010-05-04

Date de description :

Au :                              2010-05-04

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                    84.01 m

Est	630 199.9
Nord	5 374 497.8
Élévation	287.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	9.00	0.00°	0.00°	Oui
Reflex	12.00	313.50°	-59.10°	Oui
Reflex	15.00	356.10°	-59.10°	Non
Reflex	18.00	357.90°	-59.10°	Non
Reflex	21.00	357.20°	-59.20°	Non
Reflex	24.00	352.90°	-59.10°	Oui
Reflex	27.00	1.10°	-59.20°	Oui
Reflex	30.00	359.20°	-59.10°	Non
Reflex	33.00	358.20°	-59.00°	Non
Reflex	36.00	357.60°	-59.00°	Non
Reflex	39.00	357.80°	-59.00°	Non
Reflex	42.00	358.00°	-58.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	45.00	358.20°	-58.80°	Non
Reflex	48.00	358.30°	-58.90°	Non
Reflex	51.00	358.50°	-58.90°	Non
Reflex	54.00	358.60°	-58.90°	Non
Reflex	57.00	358.50°	-58.90°	Non
Reflex	60.00	358.70°	-58.90°	Non
Reflex	63.00	358.70°	-58.60°	Non
Reflex	66.00	358.60°	-58.40°	Non
Reflex	69.00	358.10°	-58.40°	Non
Reflex	72.00	357.90°	-58.50°	Non
Reflex	75.00	357.70°	-58.50°	Non
Reflex	78.00	357.90°	-58.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	15.00	MT						
		<b>Mort-terrain</b>						
15.00	84.00	SY; FIN; POR	15.00	16.50	D018601	1.50	0.012	0.012
		<b>Syénite; Grains fins; Porphyrique</b>	16.50	18.00	D018602	1.50	0.036	0.036
		Syénite porphyrique, à grains fins, avec de phénocristaux Xmm.	18.00	19.50	D018603	1.50	0.024	0.024
			19.50	21.00	D018604	1.50	0.007	0.007
			21.00	22.50	D018605	1.50	0.009	0.009
			22.50	24.00	D018606	1.50	0.020	0.020
			24.00	25.50	D018608	1.50	0.005	0.005
			25.50	27.00	D018609	1.50	0.015	0.015
			27.00	28.50	D018610	1.50	<0.005	0.001
			28.50	30.00	D018611	1.50	0.147	0.147
			30.00	31.50	D018612	1.50	0.184	0.184
			31.50	33.00	D018613	1.50	0.030	0.030
			33.00	34.50	D018614	1.50	0.313	0.313
			34.50	36.00	D018615	1.50	0.043	0.043
			36.00	37.50	D018616	1.50	0.038	0.038
			37.50	39.00	D018618	1.50	0.140	0.140
			39.00	40.50	D018619	1.50	0.475	0.475
			40.50	42.00	D018620	1.50	0.139	0.139
			42.00	43.50	D018621	1.50	0.620	0.620
			43.50	45.00	D018623	1.50	0.487	0.487
			45.00	46.50	D018624	1.50	0.090	0.090
			46.50	48.00	D018625	1.50	0.416	0.416
			48.00	49.50	D018626	1.50	0.288	0.288
			49.50	51.00	D018628	1.50	0.177	0.177
			51.00	52.50	D018629	1.50	0.244	0.244
			52.50	54.00	D018630	1.50	0.712	0.712
			54.00	55.50	D018631	1.50	0.488	0.488
			55.50	57.00	D018632	1.50	0.301	0.301
			57.00	58.50	D018633	1.50	0.759	0.759
			58.50	60.00	D018634	1.50	0.139	0.139
			60.00	61.50	D018635	1.50	1.930	1.930
			61.50	63.00	D018636	1.50	0.148	0.148

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
84.00	84.01	OM Ouverture minière Ouverture minière.	63.00	64.50	D018638	1.50	1.230		1.230
			64.50	66.00	D018639	1.50	3.490		3.490
			66.00	67.50	D018640	1.50	5.940		5.940
			67.50	69.00	D018641	1.50	2.790		2.790
			69.00	70.50	D018642	1.50	3.180		3.180
			70.50	72.00	D018643	1.50	3.390		3.390
			72.00	73.50	D018644	1.50	4.130		4.130
			73.50	75.00	D018645	1.50	6.070		6.070
			75.00	76.50	D018646	1.50	5.650		5.650
			76.50	78.00	D018648	1.50	6.700		6.700
			78.00	79.50	D018649	1.50	7.230		7.230
			79.50	81.00	D018650	1.50	1.960		1.960
			81.00	82.50	D018651	1.50	2.030		2.030
			82.50	84.00	D018652	1.50	4.060		4.060
84.01	Fin du sondage								
	Nombre d'échantillons : 46								
	Nombre d'échantillons QAQC : 6								
	Longueur totale échantillonnée : 69.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
22.50	24.00	D018607	K	1.50	1.045	1.045
36.00	37.50	D018617	D018616	1.50	0.036	0.036
42.00	42.00	D018622	M1	0.00	<0.005	0.001
48.00	48.00	D018627	L	0.00	2.080	2.080
61.50	63.00	D018637	D018636	1.50	0.180	0.180
75.00	75.00	D018647	M	0.00	3.070	3.070

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-210**

Titre minier :

Section :                      630100

Canton :

Niveau :

Foré par :              Bradley et Frères

Rang :

Place de travail :              Malartic

Décrit par :              Sylvain SAVADOGO

Lot :

Du :                      2010-05-05

Date de description :              2010-07-01

Au :                      2010-05-06

Collet

UTM

Azimut :                      0.00°

Est                              630 099.5

Plongée :                      -45.00°

Nord                              5 374 500.0

Longueur :                      113.00 m

Élévation                      281.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	345.70°	-45.00°	Oui
Reflex	8.00	345.70°	-45.00°	Oui
Reflex	11.00	343.50°	-44.80°	Oui
Reflex	14.00	358.30°	-44.50°	Oui
Reflex	17.00	352.90°	-44.50°	Oui
Reflex	20.00	0.20°	-44.00°	Non
Reflex	23.00	0.70°	-43.20°	Non
Reflex	26.00	1.00°	-42.20°	Non
Reflex	29.00	1.20°	-41.20°	Non
Reflex	32.00	1.40°	-40.60°	Non
Reflex	35.00	2.00°	-40.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	2.30°	-39.10°	Non
Reflex	41.00	2.30°	-38.10°	Non
Reflex	44.00	2.20°	-37.10°	Non
Reflex	47.00	2.20°	-35.90°	Non
Reflex	50.00	1.80°	-34.70°	Non
Reflex	53.00	1.10°	-33.80°	Non
Reflex	56.00	0.50°	-32.90°	Non
Reflex	59.00	353.40°	-32.40°	Oui
Reflex	62.00	0.50°	-32.20°	Non
Reflex	65.00	0.30°	-32.20°	Non
Reflex	68.00	0.20°	-32.10°	Non
Reflex	71.00	0.20°	-31.90°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	14.00	MT <b>Mort-terrain</b> MT							
14.00	18.00	SY; POR <b>Syénite 50°; Porphyrique</b> syénite chloriteux, modérément hématisée; contact graduel entre SY et BA; pyrite disséminée dans la matrice jusqu'à 0,2%;	14.00	15.50	D034974	1.50	0.588		0.588
			15.50	17.00	D034975	1.50	0.072		0.072
			17.00	18.50	D034976	1.50	0.161		0.161
18.00	57.50	BA; AMY <b>Basalte 50°; Amygdalaire</b> basalte cisailé, 60°AC en moyenne et partiellement très amygdalaire; Modérément carbonaté; partiellement sericitisé; pyrite disséminé entre 0,2% et 0,5% dans la matrice; Contenant des vQz-CC;							
18.00	57.50	CB05; SR02 <b>Carbonaté 5; Séricitique 2</b> modérément carbonaté; partiellement sericitique;	18.50	20.00	D034977	1.50	<0.005		0.001
			20.00	21.50	D034978	1.50	0.101		0.101
			21.50	23.00	D034979	1.50	0.691		0.691
			23.00	24.50	D034981	1.50	0.087		0.087
			24.50	26.00	D034982	1.50	0.158		0.158
			26.00	27.50	D034983	1.50	0.102		0.102
			27.50	29.00	D034984	1.50	0.406		0.406
			29.00	30.50	D034985	1.50	0.062		0.062
			30.50	32.00	D034986	1.50	0.106		0.106
			32.00	33.50	D034987	1.50	0.129		0.129
			33.50	35.00	D034988	1.50	0.392		0.392
			35.00	36.50	D034989	1.50	0.523		0.523
			36.50	38.00	D034991	1.50	1.195		1.195
			38.00	39.50	D034993	1.50	2.460		2.460
			39.50	41.00	D034996	1.50	0.047		0.047
			41.00	42.50	D034997	1.50	0.130		0.130
			42.50	44.00	D034998	1.50	<0.005		0.001
			44.00	45.50	D034999	1.50	0.005		0.005
			45.50	47.00	D035001	1.50	0.019		0.019
			47.00	48.50	D035002	1.50	<0.005		0.001
			48.50	50.00	D035003	1.50	<0.005		0.001
			50.00	51.50	D035004	1.50	<0.005		0.001
			51.50	53.00	D035005	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
57.50	82.25	BA <b>Basalte 75*</b> Basalte remplacé (REBA), modérément silicifié, partiellement modérément carbonaté, peu sericitique; zone minéralisé à la pyrite disséminée entre 0,5% et 0,8% dans la matrice; contenant des vQz-CC, 45-50*AC; dyke de syénite porphyrique avec des phénocristaux de Qz-CC automorphes et hématisés, modérément carbonatée et plus ou moins hématisée, entre 58m et 58,7m; des structure de géode sont observé entre 67m et 69m;  Contacts nets marqués par des vQz-CC, 70*AC;	53.00	54.50	D035006	1.50	<0.005		0.001
			54.50	56.00	D035007	1.50	<0.005		0.001
			56.00	57.50	D035008	1.50	0.012		0.012
57.50	65.00	SI05; CB05; SR02 <b>Silicifié 5; Carbonaté 5; Séricitique 2</b> plus ou moins à modérément silicifié; modérément carbonaté, peu sericitique;							
57.50	82.25	Py00.8 <b>Pyrite 0.8%</b> pyrite disséminé entre 0,5% et 0,8% dans la matrice.	57.50	59.00	D035009	1.50	3.340		3.340
			59.00	60.50	D035011	1.50	4.080		4.080
			60.50	62.00	D035012	1.50	3.440		3.440
			62.00	63.50	D035013	1.50	1.535		1.535
			63.50	65.00	D035014	1.50	2.000		2.000
65.00	69.50	SI05; SR02 <b>Silicifié 5; Séricitique 2</b> modérément silicifié et peu sericitique;	65.00	66.50	D035015	1.50	0.011		0.011
			66.50	68.00	D035016	1.50	0.096		0.096
			68.00	69.50	D035017	1.50	0.705		0.705
69.50	82.25	SI05; CB05; SR02 <b>Silicifié 5; Carbonaté 5; Séricitique 2</b> modérément carbonaté; modérément carbonaté; peu sericitique;	69.50	71.00	D035018	1.50	0.477		0.477
			71.00	72.50	D035019	1.50	2.670		2.670
			72.50	74.00	D035021	1.50	5.150		5.150
			74.00	75.50	D035022	1.50	7.140		7.140
			75.50	77.00	D035023	1.50	5.370		5.370
			77.00	78.50	D035024	1.50	6.230		6.230
			78.50	80.00	D035025	1.50	5.140		5.140
			80.00	81.50	D035026	1.50	4.840		4.840
81.50	83.00	D035027	1.50	5.090		5.090			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
82.25	113.00	BA <b>Basalte 60°</b> basalte cisailé, 60°AC en moyenne et partiellement très amygdalaire; Modérément carbonaté; partiellement sericitisé; pyrite disséminé à 0,2% dans la matrice; Contenant des vQz-CC;							
82.25	113.00	CB05; SR02 <b>Carbonaté 5; Séricitique 2</b> modérément carbonaté; peu sericitique;	83.00	84.50	D035028	1.50	0.033		0.033
			84.50	86.00	D035029	1.50	0.016		0.016
			86.00	87.50	D035031	1.50	0.005		0.005
			87.50	89.00	D035033	1.50	0.006		0.006
			89.00	90.50	D035034	1.50	<0.005		0.001
			90.50	92.00	D035035	1.50	<0.005		0.001
			92.00	93.50	D035036	1.50	<0.005		0.001
			93.50	95.00	D035037	1.50	<0.005		0.001
			95.00	96.50	D035038	1.50	<0.005		0.001
			96.50	98.00	D035039	1.50	<0.005		0.001
			98.00	99.50	D035041	1.50	<0.005		0.001
			99.50	101.00	D035042	1.50	<0.005		0.001
			101.00	102.50	D035043	1.50	<0.005		0.001
			102.50	104.00	D035044	1.50	<0.005		0.001
			104.00	105.50	D035045	1.50	<0.005		0.001
			105.50	107.00	D035046	1.50	<0.005		0.001
			107.00	108.50	D035047	1.50	<0.005		0.001
			108.50	110.00	D035048	1.50	<0.005		0.001
			110.00	111.50	D035049	1.50	<0.005		0.001
			111.50	113.00	D035051	1.50	<0.005		0.001
113.00		Fin du sondage Nombre d'échantillons : 66 Nombre d'échantillons QAQC : 10 Longueur totale échantillonnée : 99.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
21.50	23.00	D034980	D034979	1.50	0.662	0.662
35.00	35.00	D034990	L	0.00	2.200	2.200
36.50	36.50	D034992	M1	0.00	<0.005	0.001
44.00	45.50	D035000	D034999	1.50	<0.005	0.001
57.50	57.50	D035010	M	0.00	2.960	2.960
71.00	72.50	D035020	D035019	1.50	2.580	2.580
84.50	84.50	D035030	J	0.00	0.690	0.690
86.00	86.00	D035032	M1	0.00	<0.005	0.001
96.50	98.00	D035040	D035039	1.50	<0.005	0.001
110.00	110.00	D035050	K	0.00	1.045	1.045

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-211**

Titre minier :

Section :                      630100

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Johan Bergé

Lot :

Du :                              2010-05-06

Date de description :

Au :                              2010-05-07

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      95.01 m

Est	630 099.5
Nord	5 374 499.5
Élévation	281.4

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	341.80°	-59.10°	Oui
Reflex	8.00	3.50°	-59.10°	Oui
Reflex	11.00	349.00°	-59.20°	Oui
Reflex	14.00	356.20°	-59.30°	Oui
Reflex	17.00	0.00°	-59.30°	Non
Reflex	20.00	0.30°	-59.30°	Non
Reflex	23.00	0.60°	-59.20°	Non
Reflex	26.00	0.80°	-59.10°	Non
Reflex	29.00	1.00°	-58.90°	Non
Reflex	32.00	1.30°	-58.80°	Non
Reflex	35.00	1.30°	-58.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.40°	-58.40°	Non
Reflex	41.00	1.50°	-58.30°	Non
Reflex	44.00	1.70°	-58.10°	Non
Reflex	47.00	1.70°	-58.00°	Non
Reflex	50.00	1.70°	-57.90°	Non
Reflex	53.00	1.90°	-57.80°	Non
Reflex	56.00	1.90°	-57.80°	Non
Reflex	59.00	2.00°	-57.70°	Non
Reflex	62.00	2.10°	-57.70°	Non
Reflex	65.00	2.10°	-57.60°	Non
Reflex	68.00	2.10°	-57.60°	Non
Reflex	71.00	2.10°	-57.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.90°	-57.50°	Non					
Reflex	77.00	2.00°	-57.50°	Non					
Reflex	80.00	1.90°	-57.40°	Non					
Reflex	83.00	1.90°	-57.30°	Non					
Reflex	86.00	2.10°	-57.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	12.20	MT <b>Mort-terrain</b> Pas de carotte récupérée.						
12.20	25.60	SY <b>Syénite 30°</b> Syénite à grain fin. Très carbonaté. Réseau de cheveux/veinules/veines peu développée. Assez peu minéralisé dans les zones hématisées, minéralisée dans les zones chloritisées. Hématisé avec passage graduel vers une hématisation vers le FW de l'unité. Non magnétique.	12.20	13.50	D039126	1.30	0.100	0.100
			13.50	15.00	D039127	1.50	0.147	0.147
			15.00	16.50	D039128	1.50	0.013	0.013
			16.50	18.00	D039129	1.50	0.018	0.018
			18.00	19.50	D039131	1.50	0.009	0.009
			19.50	21.00	D039132	1.50	0.089	0.089
12.20	22.40	HM <b>Hématisé</b> Passage progressif HM->CH vers le bas de l'unité.						
19.80	20.90	FRC <b>Fracturé 10°</b> Syénite bréchifiée fracturée. Clastes de syénite dans une matrice chloriteuse.	21.00	22.40	D039134	1.40	0.005	0.005
22.40	95.00	CH <b>Chloriteux</b>	22.40	24.00	D039135	1.60	0.106	0.106
			24.00	25.60	D039136	1.60	0.080	0.080
25.60	38.10	BA <b>Basalte</b> Basalte altéré par la chlorite. Présence de hyaloclastite aux bordures des coussins. Très carbonatée. Non magnétique. Présente un cisaillement 30°.	25.60	27.00	D039137	1.40	1.345	1.345
			27.00	28.50	D039138	1.50	1.910	1.910
			28.50	30.00	D039139	1.50	0.229	0.229
			30.00	31.50	D039140	1.50	0.022	0.022
			31.50	33.00	D039141	1.50	0.008	0.008
			33.00	34.50	D039142	1.50	0.005	0.005
			34.50	36.00	D039144	1.50	0.050	0.050
		Zone de transition graduelle vers le gabbro de l'unité inférieure.	36.00	37.00	D039145	1.00	0.037	0.037
			37.00	38.10	D039146	1.10	0.006	0.006
38.10	69.90	GA <b>Gabbro</b> Gabbro à grain fin altéré par la chlorite. Très carbonatée. Présente un cisaillement 30°. Non magnétique.	38.10	39.50	D039147	1.40	0.011	0.011
			39.50	41.00	D039148	1.50	<0.005	0.001
			41.00	42.50	D039149	1.50	<0.005	0.001
			42.50	44.00	D039150	1.50	0.076	0.076
			44.00	45.50	D039151	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			45.50	47.00	D039152	1.50		0.224		0.224
			47.00	48.50	D039154	1.50		2.620		2.620
			48.50	50.00	D039155	1.50		0.165		0.165
			50.00	51.50	D039156	1.50		0.224		0.224
			51.50	53.00	D039157	1.50		0.059		0.059
			53.00	54.50	D039158	1.50		0.093		0.093
			54.50	56.00	D039159	1.50		0.339		0.339
			56.00	57.50	D039160	1.50		0.326		0.326
			57.50	59.00	D039161	1.50		0.727		0.727
			59.00	60.50	D039162	1.50		0.011		0.011
			60.50	62.00	D039164	1.50		<0.005		0.001
			62.00	63.50	D039165	1.50		0.050		0.050
			63.50	65.00	D039166	1.50		0.005		0.005
			65.00	66.50	D039167	1.50		0.005		0.005
			66.50	67.50	D039168	1.00		<0.005		0.001
			67.50	68.50	D039169	1.00		<0.005		0.001
			68.50	69.90	D039171	1.40		<0.005		0.001
69.90	95.00	BA <b>Basalte</b> Basalte altéré par la chlorite. Présence de hyaloclastite aux bordures des coussins. Très carbonatée. Non magnétique. Présente un cisaillement 30'. Le remplacement par la silice est si fort vers le FW de l'unité que la nature du protolithe n'est pas certaine à partir de 83.6m.	69.90	71.50	D039172	1.60		<0.005		0.001
			71.50	73.00	D039174	1.50		0.005		0.005
			73.00	74.00	D039175	1.00		<0.005		0.001
69.90	70.30	FAI <b>Faïlle</b> Faïlle délimitant le gabbro du basalte. Faïlle remplie par de l'altération carbonate chlorite.								
74.00	83.50	BA <b>Basalte</b> Basalte remplacé par la silice. Toujours carbonatée. Très riche en pyrite.	74.00	75.50	D039176	1.50		1.225		1.225
75.30	75.50	FRC <b>Fracturé</b>	75.50	77.00	D039177	1.50		2.930		2.930

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Passage bréchifié du basalte avec des clastes arrondis à cause du cisaillement, dans une matrice fine.  83.50      95.00      BA <b>Basalte</b> Basalte remplacé par la silice. Non carbonatée. Très riche en pyrite.				77.00	78.50	D039178	1.50	0.708		0.708
				78.50	80.00	D039179	1.50	4.140		4.140
				80.00	81.50	D039180	1.50	2.990		2.990
				81.50	82.50	D039181	1.00	1.530		1.530
				82.50	83.50	D039182	1.00	3.940		3.940
				83.50	85.00	D039184	1.50	0.305		0.305
				85.00	86.50	D039185	1.50	0.093		0.093
				86.50	88.00	D039186	1.50	1.075		1.075
				88.00	89.50	D039187	1.50	0.011		0.011
				89.50	91.00	D039188	1.50	0.012		0.012
92.70      95.00      FRC <b>Fracturé</b> Basalte très fracturé lié à la proximité avec l'ouverture minière.				91.00	92.50	D039189	1.50	0.056		0.056
				92.50	94.00	D039190	1.50	0.180		0.180
				94.00	95.00	D039191	1.00	0.030		0.030
95.00	95.01	OM <b>Ouverture minière</b> Bloc signalant un core loss à la fin du trou, probablement ouverture minière.								
95.01	Fin du sondage Nombre d'échantillons : 58 Nombre d'échantillons QAQC : 8 Longueur totale échantillonnée : 82.80									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
16.50	16.50	D039130	M1	0.00	<0.005	0.001
19.50	19.50	D039133	L	0.00	2.010	2.010
33.00	34.50	D039143	D039142	1.50	0.006	0.006
45.50	45.50	D039153	M	0.00	3.050	3.050
59.00	60.50	D039163	D039162	1.50	0.010	0.010
67.50	67.50	D039170	M1	0.00	<0.005	0.001
69.90	69.90	D039173	J	0.00	0.691	0.691
82.50	83.50	D039183	D039182	1.00	3.930	3.930



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-212**

Titre minier :

Section :                      630700

Canton :

Niveau :

Foré par :                      Bradley et frères

Rang :

Place de travail :              Malartic

Décrit par :                      Sylvain SAVADOGO

Lot :

Du :                              2010-05-10

Date de description :              2010-07-13

Au :                              2010-05-17

Collet

UTM

Azimut :                      0.00°

Plongée :                      -59.00°

Longueur :                      479.00 m

Est                              630 699.9

Nord                              5 374 187.0

Élévation                      305.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	327.80°	-57.60°	Oui
Reflex	8.00	343.20°	-58.00°	Oui
Reflex	11.00	355.90°	-58.00°	Oui
Reflex	14.00	0.30°	-58.00°	Non
Reflex	17.00	0.60°	-57.80°	Non
Reflex	20.00	359.20°	-57.90°	Non
Reflex	23.00	0.90°	-57.90°	Non
Reflex	26.00	359.60°	-57.90°	Non
Reflex	29.00	0.40°	-58.00°	Non
Reflex	32.00	359.70°	-58.00°	Non
Reflex	35.00	0.30°	-58.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.40°	-58.10°	Non
Reflex	41.00	1.20°	-58.20°	Oui
Reflex	44.00	359.40°	-58.00°	Non
Reflex	47.00	0.10°	-58.10°	Non
Reflex	50.00	0.40°	-58.10°	Non
Reflex	53.00	359.60°	-58.10°	Non
Reflex	56.00	1.30°	-58.20°	Oui
Reflex	59.00	359.20°	-58.10°	Non
Reflex	62.00	0.80°	-58.50°	Non
Reflex	65.00	1.30°	-58.30°	Oui
Reflex	68.00	0.40°	-58.60°	Non
Reflex	71.00	359.60°	-58.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.50°	-58.30°	Non
Reflex	77.00	0.40°	-58.40°	Non
Reflex	80.00	360.00°	-58.40°	Non
Reflex	83.00	1.00°	-58.40°	Non
Reflex	86.00	0.80°	-58.60°	Non
Reflex	89.00	0.80°	-58.30°	Non
Reflex	92.00	0.80°	-58.50°	Non
Reflex	95.00	1.50°	-58.40°	Non
Reflex	98.00	2.50°	-58.50°	Non
Reflex	101.00	3.40°	-58.60°	Non
Reflex	104.00	3.60°	-58.80°	Non
Reflex	107.00	2.10°	-58.50°	Non
Reflex	110.00	1.60°	-58.60°	Non
Reflex	113.00	1.90°	-58.60°	Non
Reflex	116.00	1.20°	-58.70°	Non
Reflex	119.00	0.30°	-58.50°	Non
Reflex	122.00	0.60°	-58.60°	Non
Reflex	125.00	1.10°	-58.70°	Non
Reflex	128.00	0.90°	-58.90°	Non
Reflex	131.00	2.70°	-59.00°	Non
Reflex	134.00	2.50°	-58.70°	Non
Reflex	137.00	0.40°	-58.70°	Non
Reflex	140.00	1.10°	-58.70°	Non
Reflex	143.00	2.10°	-59.00°	Non
Reflex	146.00	2.70°	-58.80°	Non
Reflex	149.00	0.80°	-58.80°	Non
Reflex	152.00	2.70°	-58.80°	Non
Reflex	155.00	2.70°	-58.70°	Non
Reflex	158.00	2.40°	-59.10°	Non
Reflex	161.00	2.10°	-58.80°	Non
Reflex	164.00	2.20°	-58.90°	Non
Reflex	167.00	2.40°	-58.90°	Non
Reflex	170.00	2.40°	-58.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	2.60°	-59.00°	Non
Reflex	176.00	1.60°	-59.10°	Oui
Reflex	179.00	4.30°	-59.00°	Non
Reflex	182.00	4.30°	-59.10°	Non
Reflex	185.00	1.70°	-58.80°	Non
Reflex	188.00	1.10°	-58.80°	Non
Reflex	191.00	3.10°	-59.20°	Non
Reflex	194.00	3.00°	-59.20°	Non
Reflex	197.00	2.70°	-59.10°	Non
Reflex	200.00	2.50°	-58.90°	Non
Reflex	203.00	3.80°	-58.90°	Non
Reflex	206.00	5.40°	-59.10°	Non
Reflex	209.00	5.10°	-59.00°	Non
Reflex	212.00	4.10°	-59.10°	Non
Reflex	215.00	3.10°	-59.00°	Non
Reflex	218.00	3.10°	-59.00°	Non
Reflex	221.00	3.60°	-59.10°	Non
Reflex	224.00	4.40°	-59.10°	Non
Reflex	227.00	6.10°	-59.20°	Non
Reflex	230.00	6.50°	-59.30°	Non
Reflex	233.00	4.10°	-59.10°	Non
Reflex	236.00	3.60°	-59.00°	Non
Reflex	239.00	4.70°	-59.30°	Non
Reflex	242.00	5.30°	-59.00°	Non
Reflex	245.00	5.60°	-58.80°	Non
Reflex	248.00	5.20°	-58.70°	Non
Reflex	251.00	5.00°	-58.70°	Non
Reflex	254.00	4.50°	-58.50°	Non
Reflex	257.00	5.20°	-58.70°	Non
Reflex	260.00	6.50°	-58.40°	Non
Reflex	263.00	7.50°	-58.50°	Non
Reflex	266.00	5.20°	-58.50°	Oui
Reflex	269.00	3.30°	-58.20°	Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	6.60°	-58.10°	Non
Reflex	275.00	6.30°	-57.80°	Non
Reflex	278.00	6.30°	-57.80°	Non
Reflex	281.00	7.30°	-58.10°	Non
Reflex	284.00	5.80°	-58.00°	Oui
Reflex	287.00	8.10°	-58.00°	Non
Reflex	290.00	8.00°	-57.90°	Non
Reflex	293.00	4.40°	-57.70°	Oui
Reflex	296.00	7.40°	-57.70°	Non
Reflex	299.00	7.80°	-58.10°	Non
Reflex	302.00	9.60°	-58.00°	Non
Reflex	305.00	8.90°	-58.10°	Non
Reflex	308.00	9.50°	-58.00°	Non
Reflex	311.00	8.90°	-58.00°	Non
Reflex	314.00	9.10°	-58.30°	Non
Reflex	317.00	8.50°	-58.00°	Non
Reflex	320.00	8.50°	-58.10°	Non
Reflex	323.00	9.10°	-58.10°	Non
Reflex	326.00	8.70°	-58.00°	Non
Reflex	329.00	8.80°	-57.90°	Non
Reflex	332.00	7.10°	-58.20°	Non
Reflex	335.00	7.90°	-58.10°	Non
Reflex	338.00	8.40°	-58.20°	Non
Reflex	341.00	9.10°	-58.10°	Non
Reflex	344.00	6.50°	-58.00°	Non
Reflex	347.00	6.70°	-57.90°	Non
Reflex	350.00	7.60°	-58.30°	Non
Reflex	353.00	7.30°	-58.30°	Non
Reflex	356.00	7.70°	-58.00°	Non
Reflex	359.00	8.40°	-58.10°	Non
Reflex	362.00	9.90°	-58.10°	Non
Reflex	365.00	9.30°	-58.00°	Non
Reflex	368.00	7.60°	-57.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	8.00°	-58.30°	Non
Reflex	374.00	7.10°	-58.10°	Non
Reflex	377.00	7.30°	-58.00°	Non
Reflex	380.00	7.20°	-58.00°	Non
Reflex	383.00	6.00°	-57.80°	Non
Reflex	386.00	6.80°	-57.80°	Non
Reflex	389.00	7.60°	-58.00°	Non
Reflex	392.00	7.80°	-57.50°	Non
Reflex	395.00	6.80°	-57.80°	Oui
Reflex	398.00	8.40°	-57.90°	Non
Reflex	401.00	9.60°	-57.80°	Non
Reflex	404.00	11.70°	-58.00°	Non
Reflex	407.00	8.10°	-58.00°	Oui
Reflex	410.00	10.10°	-57.80°	Non
Reflex	413.00	9.80°	-57.80°	Non
Reflex	416.00	11.80°	-57.80°	Non
Reflex	419.00	9.30°	-57.80°	Non
Reflex	422.00	9.30°	-58.00°	Non
Reflex	425.00	10.80°	-57.90°	Non
Reflex	428.00	8.70°	-57.80°	Oui
Reflex	431.00	9.10°	-57.70°	Non
Reflex	434.00	11.00°	-58.00°	Non
Reflex	437.00	9.40°	-57.80°	Non
Reflex	440.00	10.90°	-57.50°	Non
Reflex	443.00	8.70°	-57.40°	Oui
Reflex	446.00	11.50°	-57.40°	Non
Reflex	449.00	11.90°	-57.30°	Non
Reflex	452.00	10.30°	-57.00°	Non
Reflex	455.00	10.40°	-56.80°	Non
Reflex	458.00	9.10°	-56.80°	Non
Reflex	461.00	10.90°	-56.90°	Non
Reflex	464.00	9.40°	-56.80°	Non
Reflex	467.00	11.00°	-56.80°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	9.10°	-56.50°	Non					
Reflex	473.00	10.10°	-56.50°	Non					
Reflex	476.00	7.90°	-56.60°	Non					
Reflex	479.00	7.80°	-56.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	11.80	MT <b>Mort-terrain</b> MT							
11.80	35.00	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2% dans la matrice;							
11.80	35.00	HM05; CH02; SR02 <b>Hématisé 5; Chloriteux 2; Séricitique 2</b> modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique;	11.80	13.00	D035618	1.20	0.075		0.075
			13.00	14.00	D035619	1.00	0.226		0.226
			14.00	15.50	D035621	1.50	0.109		0.109
			15.50	17.00	D035622	1.50	0.121		0.121
			17.00	18.50	D035623	1.50	0.236		0.236
			18.50	20.00	D035624	1.50	0.574		0.574
			20.00	21.50	D035625	1.50	0.306		0.306
			21.50	23.00	D035626	1.50	0.147		0.147
			23.00	24.50	D035627	1.50	0.459		0.459
			24.50	26.00	D035628	1.50	0.318		0.318
			26.00	27.50	D035629	1.50	0.273		0.273
			27.50	29.00	D035631	1.50	0.584		0.584
			29.00	30.50	D035633	1.50	0.291		0.291
			30.50	32.00	D035634	1.50	0.101		0.101
			32.00	33.50	D035635	1.50	0.966		0.966
			33.50	35.00	D035636	1.50	0.148		0.148
35.00	42.50	SY <b>Syénite</b> syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; plus ou moins sericitique, modérément hématisé; cristaux fins de pyrite disséminée dans la matrice jusqu'à 0,8%; vQz fumée; veinules de Qz en réseau;							
35.00	42.50	SR03; HM05 <b>Séricitique 3; Hématisé 5</b> plus ou moins sericitique; modérément chloriteux;							
35.00	42.50	Py00.8 <b>Pyrite 0.8%</b> cristaux fins de pyrite disséminée jusqu'à 0,8%;	35.00	36.50	D035637	1.50	0.906		0.906
			36.50	38.00	D035638	1.50	0.434		0.434

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
42.50	123.00	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2% dans la matrice;	38.00	39.50	D035639	1.50	1.255		1.255
			39.50	41.00	D035641	1.50	1.575		1.575
			41.00	42.50	D035642	1.50	4.160		4.160
42.50	123.00	HM05; CH02; SR02 <b>Hématisé 5; Chloriteux 2; Séricitique 2</b> modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique;	42.50	44.00	D035643	1.50	2.150		2.150
			44.00	45.50	D035644	1.50	0.012		0.012
			45.50	47.00	D035645	1.50	0.008		0.008
			47.00	48.50	D035646	1.50	0.006		0.006
			48.50	50.00	D035647	1.50	0.172		0.172
			50.00	51.50	D035648	1.50	0.006		0.006
			51.50	53.00	D035649	1.50	<0.005		0.001
			53.00	54.50	D035651	1.50	0.006		0.006
			54.50	56.00	D035652	1.50	0.068		0.068
			56.00	57.50	D035653	1.50	0.012		0.012
			57.50	59.00	D035654	1.50	<0.005		0.001
			59.00	60.50	D035655	1.50	<0.005		0.001
			60.50	62.00	D035656	1.50	<0.005		0.001
			62.00	63.50	D035657	1.50	<0.005		0.001
			63.50	65.00	D035658	1.50	<0.005		0.001
			65.00	66.50	D035659	1.50	0.418		0.418
			66.50	68.00	D035661	1.50	1.195		1.195
			68.00	69.50	D035662	1.50	1.085		1.085
			69.50	71.00	D035663	1.50	0.528		0.528
			71.00	72.50	D035664	1.50	0.005		0.005
72.50	74.00	D035665	1.50	<0.005		0.001			
74.00	75.50	D035666	1.50	0.005		0.005			
75.50	77.00	D035667	1.50	<0.005		0.001			
77.00	78.50	D035668	1.50	<0.005		0.001			
78.50	80.00	D035669	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	80.00	81.50	D035671	1.50	<0.005		0.001
	81.50	83.00	D035673	1.50	<0.005		0.001
	83.00	84.50	D035674	1.50	<0.005		0.001
	84.50	86.00	D035675	1.50	<0.005		0.001
	86.00	87.50	D035676	1.50	0.013		0.013
	87.50	89.00	D035677	1.50	<0.005		0.001
	89.00	90.50	D035678	1.50	<0.005		0.001
	90.50	92.00	D035679	1.50	<0.005		0.001
	92.00	93.50	D035681	1.50	<0.005		0.001
	93.50	95.00	D035682	1.50	<0.005		0.001
	95.00	96.50	D035683	1.50	<0.005		0.001
	96.50	98.00	D035684	1.50	<0.005		0.001
	98.00	99.50	D035685	1.50	<0.005		0.001
	99.50	101.00	D035686	1.50	<0.005		0.001
	101.00	102.50	D035687	1.50	<0.005		0.001
	102.50	104.00	D035688	1.50	<0.005		0.001
	104.00	105.50	D035689	1.50	<0.005		0.001
	105.50	107.00	D035691	1.50	<0.005		0.001
	107.00	108.50	D035692	1.50	<0.005		0.001
	108.50	110.00	D035693	1.50	<0.005		0.001
	110.00	111.50	D035694	1.50	<0.005		0.001
	111.50	113.00	D035695	1.50	<0.005		0.001
	113.00	114.50	D035696	1.50	0.005		0.005
	114.50	116.00	D035697	1.50	<0.005		0.001
	116.00	117.50	D035698	1.50	<0.005		0.001
	117.50	119.00	D035699	1.50	<0.005		0.001
	119.00	120.50	D035701	1.50	<0.005		0.001
	120.50	122.00	D035702	1.50	<0.005		0.001
	122.00	123.50	D035703	1.50	<0.005		0.001
123.00      192.50      SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; plus ou moins et modérément carbonaté; modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique; cristaux de							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
123.00	192.50	pyrite disséminé jusqu'à 0,2% dans la matrice; CB05; HM05; CH02; SR02	123.50	125.00	D035704	1.50	0.008		0.008
		<b>Carbonaté 5; Hématisé 5; Chloriteux 2; Séricitique 2</b>	125.00	126.50	D035705	1.50	<0.005		0.001
		plus ou moins à modérément carbonaté; modérément hématisé;	126.50	128.00	D035706	1.50	0.311		0.311
		partiellement peu chloriteux; partiellement peu sericitique;	128.00	129.50	D035707	1.50	0.013		0.013
			129.50	131.00	D035708	1.50	<0.005		0.001
			131.00	132.50	D035709	1.50	<0.005		0.001
			132.50	134.00	D035711	1.50	<0.005		0.001
			134.00	135.50	D035713	1.50	<0.005		0.001
			135.50	137.00	D035714	1.50	<0.005		0.001
			137.00	138.50	D035715	1.50	<0.005		0.001
			138.50	140.00	D035716	1.50	<0.005		0.001
			140.00	141.50	D035717	1.50	<0.005		0.001
			141.50	143.00	D035718	1.50	<0.005		0.001
			143.00	144.50	D035719	1.50	<0.005		0.001
			144.50	146.00	D035721	1.50	<0.005		0.001
			146.00	147.50	D035722	1.50	0.008		0.008
			147.50	149.00	D035723	1.50	<0.005		0.001
			149.00	150.50	D035724	1.50	0.022		0.022
			150.50	152.00	D035725	1.50	0.019		0.019
			152.00	153.50	D035726	1.50	<0.005		0.001
			153.50	155.00	D035727	1.50	<0.005		0.001
			155.00	156.50	D035728	1.50	0.013		0.013
			156.50	158.00	D035729	1.50	<0.005		0.001
			158.00	159.50	D035731	1.50	<0.005		0.001
			159.50	161.00	D035732	1.50	<0.005		0.001
			161.00	162.50	D035733	1.50	<0.005		0.001
			162.50	164.00	D035734	1.50	<0.005		0.001
			164.00	165.50	D035735	1.50	<0.005		0.001
			165.50	167.00	D035736	1.50	<0.005		0.001
			167.00	168.50	D035737	1.50	<0.005		0.001
			168.50	170.00	D035738	1.50	<0.005		0.001
			170.00	171.50	D035739	1.50	<0.005		0.001
			171.50	173.00	D035741	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			173.00	174.50	D035742	1.50	<0.005		0.001
			174.50	176.00	D035743	1.50	<0.005		0.001
			176.00	177.50	D035744	1.50	<0.005		0.001
			177.50	179.00	D035745	1.50	<0.005		0.001
			179.00	180.50	D035746	1.50	<0.005		0.001
			180.50	182.00	D035747	1.50	<0.005		0.001
			182.00	183.50	D035748	1.50	<0.005		0.001
			183.50	185.00	D035749	1.50	<0.005		0.001
			185.00	186.50	D035751	1.50	<0.005		0.001
			186.50	188.00	D035753	1.50	<0.005		0.001
			188.00	189.50	D035754	1.50	<0.005		0.001
			189.50	191.00	D035755	1.50	0.005		0.005
			191.00	192.50	D035756	1.50	0.062		0.062
192.50	210.00	SY; CAT; POR	192.50	194.00	D035757	1.50	0.014		0.014
		<b>Syénite; Cataclasée; Porphyrique</b>	194.00	195.50	D035758	1.50	0.006		0.006
		syénite partiellement cataclasée; modérément hématisé; peu	195.50	197.00	D035759	1.50	0.016		0.016
		chloriteux; peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2%	197.00	198.50	D035761	1.50	1.635		1.635
		dans la matrice; cristaux de pyrite disséminé à 0,8% dans une matrice	198.50	200.00	D035762	1.50	0.048		0.048
		silicifiée, séricitisée et chloriteuse;							
192.50	200.00	HM05; CH02; SR02							
		<b>Hématisé 5; Chloriteux 2; Séricitique 2</b>							
		modérément hématisé; partiellement peu sericitisé; partiellement							
		peu chloriteux;							
200.00	213.50	CB05; HM05; SR02; CH02	200.00	201.50	D035763	1.50	0.009		0.009
		<b>Carbonaté 5; Hématisé 5; Séricitique 2; Chloriteux 2</b>	201.50	203.00	D035764	1.50	0.073		0.073
		plus ou moins à modérément carbonaté; modérément hématisé;	203.00	204.50	D035765	1.50	0.064		0.064
		partiellement peu chloriteux; partiellement peu sericitique;	204.50	206.00	D035766	1.50	0.039		0.039
			206.00	207.50	D035767	1.50	<0.005		0.001
			207.50	209.00	D035768	1.50	<0.005		0.001
			209.00	210.50	D035769	1.50	<0.005		0.001
210.00	236.00	SY; CAT; POR	210.50	212.00	D035771	1.50	<0.005		0.001
		<b>Syénite; Cataclasée; Porphyrique</b>	212.00	213.50	D035772	1.50	0.029		0.029
		syénite cataclasée avec des fragment de syénite anguleux et							
		porphyrique avec des phénocristaux moyens et grossiers de Fp; plus							
		ou moins et modérément carbonaté; modérément hématisé; peu							
		chloriteux; peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2%							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
dans la matrice; contenant des quelques veines de Qz;									
213.50	216.50	HM05; SR02; CH02	213.50	215.00	D035773	1.50	<0.005		0.001
		<b>Hématisé 5; Séricitique 2; Chloriteux 2</b>	215.00	216.50	D035774	1.50	<0.005		0.001
		modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique;							
216.50	343.00	CB05; HM05; SR02; CH02	216.50	218.00	D035775	1.50	<0.005		0.001
		<b>Carbonaté 5; Hématisé 5; Séricitique 2; Chloriteux 2</b>	218.00	219.50	D035776	1.50	<0.005		0.001
		plus ou moins à modérément carbonaté; modérément hématisé; partiellement peu chloriteux; partiellement peu sericitique;	219.50	221.00	D035777	1.50	<0.005		0.001
			221.00	222.50	D035778	1.50	<0.005		0.001
			222.50	224.00	D035779	1.50	<0.005		0.001
			224.00	225.50	D035781	1.50	<0.005		0.001
			225.50	227.00	D035782	1.50	<0.005		0.001
			227.00	228.50	D035783	1.50	<0.005		0.001
			228.50	230.00	D035784	1.50	<0.005		0.001
			230.00	231.50	D035785	1.50	<0.005		0.001
			231.50	233.00	D035786	1.50	<0.005		0.001
			233.00	234.50	D035787	1.50	<0.005		0.001
			234.50	236.00	D035788	1.50	<0.005		0.001
236.00	268.00	SY; POR	236.00	237.50	D035789	1.50	<0.005		0.001
		<b>Syénite; Porphyrique</b>	237.50	239.00	D035791	1.50	<0.005		0.001
		syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; plus ou moins et modérément carbonaté; modérément hématisé; peu chloriteux; peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2% dans la matrice; contenant une zone de Qz-CC injecté avec de la CHL, SR entre 254m et 255m;	239.00	240.50	D035793	1.50	<0.005		0.001
			240.50	242.00	D035794	1.50	<0.005		0.001
			242.00	243.50	D035795	1.50	<0.005		0.001
			243.50	245.00	D035796	1.50	<0.005		0.001
			245.00	246.50	D035797	1.50	<0.005		0.001
			246.50	248.00	D035798	1.50	<0.005		0.001
			248.00	249.50	D035799	1.50	<0.005		0.001
			249.50	251.00	D035801	1.50	<0.005		0.001
			251.00	252.50	D035802	1.50	<0.005		0.001
			252.50	254.00	D035803	1.50	<0.005		0.001
			254.00	255.50	D035804	1.50	<0.005		0.001
			255.50	257.00	D035805	1.50	<0.005		0.001
			257.00	258.50	D035806	1.50	<0.005		0.001
			258.50	260.00	D035807	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
268.00	271.00	SY <b>Syénite</b> syénite bréchifiée; c'est une brèche de fracture; il n'y a pas de silicification liée à cette bréchification; modérément carbonaté; modérément hématisé; peu chloriteux; peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2% dans la matrice;	260.00	261.50	D035808	1.50	0.008		0.008
			261.50	263.00	D035809	1.50	0.011		0.011
			263.00	264.50	D035811	1.50	<0.005		0.001
			264.50	266.00	D035812	1.50	<0.005		0.001
			266.00	267.50	D035813	1.50	<0.005		0.001
			267.50	269.00	D035814	1.50	0.027		0.027
			269.00	270.50	D035815	1.50	0.021		0.021
			270.50	272.00	D035816	1.50	0.010		0.010
271.00	343.00	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique avec des phénocristaux moyens et grossiers de Fp; plus ou moins et modérément carbonaté; modérément hématisé; peu chloriteux; peu sericitique; cristaux de pyrite disséminé jusqu'à 0,2% dans la matrice; contenant quelques vQz;	272.00	273.50	D035817	1.50	<0.005		0.001
			273.50	275.00	D035818	1.50	0.016		0.016
			275.00	276.50	D035819	1.50	0.389		0.389
			276.50	278.00	D035821	1.50	0.374		0.374
			278.00	279.50	D035822	1.50	0.217		0.217
			279.50	281.00	D035823	1.50	<0.005		0.001
			281.00	282.50	D035824	1.50	0.022		0.022
			282.50	284.00	D035825	1.50	<0.005		0.001
			284.00	285.50	D035826	1.50	0.019		0.019
			285.50	287.00	D035827	1.50	<0.005		0.001
			287.00	288.50	D035828	1.50	<0.005		0.001
			288.50	290.00	D035829	1.50	<0.005		0.001
			290.00	291.50	D035831	1.50	<0.005		0.001
			291.50	293.00	D035833	1.50	<0.005		0.001
			293.00	294.50	D035834	1.50	<0.005		0.001
			294.50	296.00	D035835	1.50	0.006		0.006
			296.00	297.50	D035836	1.50	<0.005		0.001
			297.50	299.00	D035837	1.50	<0.005		0.001
299.00	300.50	D035838	1.50	<0.005		0.001			
300.50	302.00	D035839	1.50	<0.005		0.001			
302.00	303.50	D035841	1.50	<0.005		0.001			
303.50	305.00	D035842	1.50	0.007		0.007			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			305.00	306.50	D035843	1.50	<0.005		0.001
			306.50	308.00	D035844	1.50	<0.005		0.001
			308.00	309.50	D035845	1.50	0.005		0.005
			309.50	311.00	D035846	1.50	0.030		0.030
			311.00	312.50	D035847	1.50	0.020		0.020
			312.50	314.00	D035848	1.50	0.010		0.010
			314.00	315.50	D035849	1.50	0.039		0.039
			315.50	317.00	D035851	1.50	<0.005		0.001
			317.00	318.50	D035852	1.50	<0.005		0.001
			318.50	320.00	D035853	1.50	0.206		0.206
			320.00	321.50	D035854	1.50	0.008		0.008
			321.50	323.00	D035855	1.50	0.289		0.289
			323.00	324.50	D035856	1.50	0.161		0.161
			324.50	326.00	D035857	1.50	0.153		0.153
			326.00	327.50	D035858	1.50	0.337		0.337
			327.50	329.00	D035859	1.50	0.062		0.062
			329.00	330.50	D035861	1.50	<0.005		0.001
			330.50	332.00	D035862	1.50	<0.005		0.001
			332.00	333.50	D035863	1.50	<0.005		0.001
			333.50	335.00	D035864	1.50	<0.005		0.001
			335.00	336.50	D035865	1.50	<0.005		0.001
			336.50	338.00	D035866	1.50	<0.005		0.001
			338.00	339.50	D035867	1.50	<0.005		0.001
			339.50	341.00	D035868	1.50	0.006		0.006
			341.00	342.50	D035869	1.50	0.201		0.201
			342.50	344.00	D035871	1.50	0.195		0.195
343.00	479.00	SY; SY <b>Syénite; Syénite</b> Syénite contenant rarement à peu de phénocristaux de FP; modérément carbonaté; des passages redondants peu et plus ou moins sericitique et peu à plus ou moins chloriteux; fin cristaux de pyrite disséminée entre 0,2 à 0,8% la matrice des passages sericitiques; contenant des vQz-CC et des veinules de Qz-CC orienté par endroit;							
343.00	479.00	CB05; SR03; CH03							

Corporation Minière Osisko Div. Exploration

Description		Analyse						
		De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
343.00	479.00	<b>Carbonaté 5; Séricitique 3; Chloriteux 3</b>						
		modérément carbonaté avec des passages non carbonatés; partiellement peu et plus ou moins sericitique; partiellement peu et plus ou moins chloriteux;						
		Py00.8						
		<b>Pyrite 0.8%</b>						
		fin cristaux de pyrite disséminée dans la matrice entre 0,2% à 0,8%;						
		344.00	345.50	D035873	1.50	0.178		0.178
		345.50	347.00	D035874	1.50	0.016		0.016
		347.00	348.50	D035875	1.50	0.020		0.020
		348.50	350.00	D035876	1.50	<0.005		0.001
		350.00	351.50	D035877	1.50	0.194		0.194
		351.50	353.00	D035878	1.50	0.624		0.624
		353.00	354.50	D035879	1.50	0.486		0.486
		354.50	356.00	D035881	1.50	0.022		0.022
		356.00	357.50	D035882	1.50	0.021		0.021
		357.50	359.00	D035883	1.50	0.057		0.057
		359.00	360.50	D035884	1.50	0.172		0.172
		360.50	362.00	D035885	1.50	0.270		0.270
		362.00	363.50	D035886	1.50	0.203		0.203
		363.50	365.00	D035887	1.50	1.415		1.415
		365.00	366.50	D035888	1.50	0.261		0.261
366.50	368.00	D035889	1.50	0.011		0.011		
368.00	369.50	D035891	1.50	0.075		0.075		
369.50	371.00	D035892	1.50	<0.005		0.001		
371.00	372.50	D035893	1.50	<0.005		0.001		
372.50	374.00	D035894	1.50	0.205		0.205		
374.00	375.50	D035895	1.50	0.157		0.157		
375.50	377.00	D035896	1.50	0.353		0.353		
377.00	378.50	D035897	1.50	0.029		0.029		
378.50	380.00	D035898	1.50	0.006		0.006		
380.00	381.50	D035899	1.50	0.409		0.409		
381.50	383.00	D035901	1.50	1.390		1.390		
383.00	384.50	D035902	1.50	0.026		0.026		
384.50	386.00	D035903	1.50	0.024		0.024		
386.00	387.50	D035904	1.50	0.035		0.035		
387.50	389.00	D035905	1.50	0.172		0.172		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	389.00	390.50	D035906	1.50	0.026		0.026
	390.50	392.00	D035907	1.50	0.012		0.012
	392.00	393.50	D035908	1.50	<0.005		0.001
	393.50	395.00	D035909	1.50	0.023		0.023
	395.00	396.50	D035911	1.50	<0.005		0.001
	396.50	398.00	D035913	1.50	0.013		0.013
	398.00	399.50	D035914	1.50	0.007		0.007
	399.50	401.00	D035915	1.50	<0.005		0.001
	401.00	402.50	D035916	1.50	0.033		0.033
	402.50	404.00	D035917	1.50	0.157		0.157
	404.00	405.50	D035918	1.50	1.135		1.135
	405.50	407.00	D035919	1.50	0.086		0.086
	407.00	408.50	D035921	1.50	0.102		0.102
	408.50	410.00	D035922	1.50	0.021		0.021
	410.00	411.50	D035923	1.50	0.723		0.723
	411.50	413.00	D035924	1.50	0.237		0.237
	413.00	414.50	D035925	1.50	0.083		0.083
	414.50	416.00	D035926	1.50	0.076		0.076
	416.00	417.50	D035927	1.50	0.200		0.200
	417.50	419.00	D035928	1.50	0.120		0.120
	419.00	420.50	D035929	1.50	0.020		0.020
	420.50	422.00	D035931	1.50	<0.005		0.001
	422.00	423.50	D035932	1.50	0.130		0.130
	423.50	425.00	D035933	1.50	0.188		0.188
	425.00	426.50	D035934	1.50	0.018		0.018
	426.50	428.00	D035935	1.50	<0.005		0.001
	428.00	429.50	D035936	1.50	<0.005		0.001
	429.50	431.00	D035937	1.50	<0.005		0.001
	431.00	432.50	D035938	1.50	0.032		0.032
	432.50	434.00	D035939	1.50	0.059		0.059
	434.00	435.50	D035941	1.50	0.006		0.006
	435.50	437.00	D035942	1.50	0.145		0.145
	437.00	438.50	D035943	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	438.50	440.00	D035944	1.50	0.007		0.007
	440.00	441.50	D035945	1.50	0.059		0.059
	441.50	443.00	D035946	1.50	<0.005		0.001
	443.00	444.50	D035947	1.50	<0.005		0.001
	444.50	446.00	D035948	1.50	0.025		0.025
	446.00	447.50	D035949	1.50	0.011		0.011
	447.50	449.00	D035951	1.50	0.052		0.052
	449.00	450.50	D035953	1.50	0.017		0.017
	450.50	452.00	D035954	1.50	<0.005		0.001
	452.00	453.50	D035955	1.50	<0.005		0.001
	453.50	455.00	D035956	1.50	0.526		0.526
	455.00	456.50	D035957	1.50	0.660		0.660
	456.50	458.00	D035958	1.50	0.235		0.235
	458.00	459.50	D035959	1.50	0.629		0.629
	459.50	461.00	D035961	1.50	0.062		0.062
	461.00	462.50	D035962	1.50	0.013		0.013
	462.50	464.00	D035963	1.50	0.023		0.023
	464.00	465.50	D035964	1.50	0.017		0.017
	465.50	467.00	D035965	1.50	0.701		0.701
	467.00	468.50	D035966	1.50	0.691		0.691
	468.50	470.00	D035967	1.50	0.241		0.241
	470.00	471.50	D035968	1.50	0.299		0.299
	471.50	473.00	D035969	1.50	1.155		1.155
	473.00	474.50	D035971	1.50	0.218		0.218
	474.50	476.00	D035972	1.50	0.237		0.237
	476.00	477.50	D035973	1.50	0.152		0.152
	477.50	479.00	D035974	1.50	0.116		0.116
479.00	Fin du sondage Nombre d'échantillons : 312 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 467.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
13.00	14.00	D035620	D035619	1.00	0.322	0.322
26.00	26.00	D035630	L	0.00	2.160	2.160
27.50	27.50	D035632	M1	0.00	0.006	0.006
38.00	39.50	D035640	D035639	1.50	1.275	1.275
51.50	51.50	D035650	M	0.00	3.190	3.190
65.00	66.50	D035660	D035659	1.50	0.497	0.497
78.50	78.50	D035670	J	0.00	0.580	0.580
80.00	80.00	D035672	M1	0.00	0.006	0.006
90.50	92.00	D035680	D035679	1.50	<0.005	0.001
104.00	104.00	D035690	K	0.00	1.080	1.080
117.50	119.00	D035700	D035699	1.50	<0.005	0.001
131.00	131.00	D035710	L	0.00	2.220	2.220
132.50	132.50	D035712	M1	0.00	<0.005	0.001
143.00	144.50	D035720	D035719	1.50	<0.005	0.001
156.50	156.50	D035730	M	0.00	3.080	3.080
170.00	171.50	D035740	D035739	1.50	<0.005	0.001
183.50	183.50	D035750	J	0.00	0.716	0.716
185.00	185.00	D035752	M1	0.00	<0.005	0.001
195.50	197.00	D035760	D035759	1.50	0.017	0.017
209.00	209.00	D035770	K	0.00	1.040	1.040
222.50	224.00	D035780	D035779	1.50	<0.005	0.001
236.00	236.00	D035790	L	0.00	2.070	2.070
237.50	237.50	D035792	M1	0.00	<0.005	0.001
248.00	249.50	D035800	D035799	1.50	<0.005	0.001
261.50	261.50	D035810	M	0.00	3.310	3.310
275.00	276.50	D035820	D035819	1.50	0.475	0.475
288.50	288.50	D035830	J	0.00	0.835	0.835
290.00	290.00	D035832	M1	0.00	<0.005	0.001
300.50	302.00	D035840	D035839	1.50	<0.005	0.001
314.00	314.00	D035850	K	0.00	1.165	1.165
327.50	329.00	D035860	D035859	1.50	0.049	0.049
341.00	341.00	D035870	L	0.00	2.200	2.200
342.50	342.50	D035872	M1	0.00	<0.005	0.001



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
353.00	354.50	D035880	D035879	1.50	0.484	0.484
366.50	366.50	D035890	M	0.00	3.370	3.370
380.00	381.50	D035900	D035899	1.50	0.382	0.382
393.50	393.50	D035910	J	0.00	0.851	0.851
395.00	395.00	D035912	M1	0.00	<0.005	0.001
405.50	407.00	D035920	D035919	1.50	0.118	0.118
419.00	419.00	D035930	K	0.00	1.065	1.065
432.50	434.00	D035940	D035939	1.50	0.072	0.072
446.00	446.00	D035950	L	0.00	2.250	2.250
447.50	447.50	D035952	M1	0.00	<0.005	0.001
458.00	459.50	D035960	D035959	1.50	0.638	0.638
471.50	471.50	D035970	M	0.00	3.020	3.020

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-213**

Titre minier :

Section :                      630700

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Ciara Cooke

Lot :

Du :                              2010-05-04

Date de description :

Au :                              2010-05-10

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -57.00°  
 Longueur :                      431.20 m

Est	630 699.8
Nord	5 374 186.7
Élévation	305.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	309.20°	-78.40°	Oui
Reflex	8.00	227.70°	-78.60°	Oui
Reflex	11.00	349.20°	-65.80°	Oui
Reflex	14.00	348.10°	-65.60°	Oui
Reflex	17.00	358.70°	-66.90°	Non
Reflex	20.00	357.20°	-61.20°	Non
Reflex	23.00	358.60°	-60.10°	Non
Reflex	26.00	359.50°	-65.80°	Non
Reflex	29.00	359.40°	-65.90°	Non
Reflex	32.00	359.40°	-65.90°	Non
Reflex	35.00	0.50°	-66.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.60°	-65.80°	Non
Reflex	41.00	359.70°	-66.00°	Non
Reflex	44.00	359.50°	-65.90°	Non
Reflex	47.00	0.70°	-66.90°	Non
Reflex	50.00	1.10°	-67.20°	Oui
Reflex	53.00	359.70°	-65.70°	Non
Reflex	56.00	360.00°	-66.00°	Non
Reflex	59.00	359.80°	-66.00°	Non
Reflex	62.00	0.60°	-65.90°	Non
Reflex	65.00	357.80°	-68.50°	Non
Reflex	68.00	0.10°	-65.90°	Non
Reflex	71.00	359.40°	-65.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	359.90°	-65.90°	Non	Reflex	173.00	0.30°	-65.70°	Non
Reflex	77.00	359.90°	-65.80°	Non	Reflex	176.00	0.60°	-65.70°	Non
Reflex	80.00	359.70°	-65.80°	Non	Reflex	179.00	0.20°	-65.60°	Non
Reflex	83.00	359.10°	-65.60°	Non	Reflex	182.00	359.90°	-65.70°	Non
Reflex	86.00	359.60°	-65.80°	Non	Reflex	185.00	359.90°	-65.70°	Non
Reflex	89.00	360.00°	-66.20°	Non	Reflex	188.00	359.70°	-65.60°	Non
Reflex	92.00	0.30°	-66.30°	Non	Reflex	191.00	359.90°	-65.60°	Non
Reflex	95.00	359.70°	-65.70°	Non	Reflex	194.00	0.10°	-65.60°	Non
Reflex	98.00	359.70°	-65.80°	Non	Reflex	197.00	359.80°	-65.60°	Non
Reflex	101.00	0.90°	-65.80°	Non	Reflex	200.00	358.30°	-63.40°	Non
Reflex	104.00	359.40°	-65.90°	Non	Reflex	203.00	359.90°	-65.60°	Non
Reflex	107.00	0.50°	-65.90°	Non	Reflex	206.00	358.90°	-65.70°	Non
Reflex	110.00	0.70°	-65.90°	Non	Reflex	209.00	359.70°	-65.60°	Non
Reflex	113.00	359.40°	-58.80°	Non	Reflex	212.00	359.10°	-65.60°	Non
Reflex	116.00	0.30°	-66.00°	Non	Reflex	215.00	359.00°	-65.50°	Non
Reflex	119.00	359.30°	-65.90°	Non	Reflex	218.00	359.60°	-65.50°	Non
Reflex	122.00	359.60°	-65.90°	Non	Reflex	221.00	359.20°	-65.40°	Non
Reflex	125.00	359.90°	-66.10°	Non	Reflex	224.00	359.60°	-65.40°	Non
Reflex	128.00	359.50°	-65.90°	Non	Reflex	227.00	359.90°	-65.40°	Non
Reflex	131.00	359.60°	-66.30°	Non	Reflex	230.00	359.80°	-65.40°	Non
Reflex	134.00	359.60°	-65.90°	Non	Reflex	233.00	359.80°	-65.30°	Non
Reflex	137.00	359.00°	-65.80°	Non	Reflex	236.00	0.80°	-65.40°	Non
Reflex	140.00	358.90°	-65.80°	Non	Reflex	239.00	0.60°	-65.40°	Non
Reflex	143.00	359.40°	-65.60°	Non	Reflex	242.00	0.60°	-65.30°	Non
Reflex	146.00	359.10°	-65.80°	Non	Reflex	245.00	1.90°	-65.40°	Oui
Reflex	149.00	359.20°	-65.70°	Non	Reflex	248.00	359.50°	-65.40°	Non
Reflex	152.00	359.80°	-66.40°	Non	Reflex	251.00	359.90°	-65.30°	Non
Reflex	155.00	0.90°	-67.20°	Non	Reflex	254.00	0.90°	-65.30°	Non
Reflex	158.00	359.80°	-65.70°	Non	Reflex	257.00	1.70°	-65.30°	Oui
Reflex	161.00	360.00°	-65.70°	Non	Reflex	260.00	0.40°	-65.30°	Non
Reflex	164.00	0.40°	-65.70°	Non	Reflex	263.00	0.70°	-65.30°	Non
Reflex	167.00	359.80°	-65.70°	Non	Reflex	266.00	0.50°	-65.30°	Non
Reflex	170.00	0.40°	-65.70°	Non	Reflex	269.00	1.00°	-65.20°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	357.50°	-65.80°	Non	Reflex	371.00	3.00°	-64.30°	Non
Reflex	275.00	359.50°	-65.20°	Non	Reflex	374.00	2.90°	-64.30°	Non
Reflex	278.00	0.80°	-65.20°	Non	Reflex	377.00	2.00°	-64.30°	Non
Reflex	281.00	0.90°	-65.20°	Non	Reflex	380.00	2.60°	-64.30°	Non
Reflex	284.00	0.50°	-65.10°	Non	Reflex	383.00	2.80°	-64.30°	Non
Reflex	287.00	1.20°	-65.10°	Non	Reflex	386.00	2.70°	-64.30°	Non
Reflex	290.00	360.00°	-65.10°	Non	Reflex	389.00	2.20°	-64.20°	Non
Reflex	293.00	359.50°	-65.10°	Non	Reflex	392.00	1.50°	-64.30°	Non
Reflex	296.00	359.00°	-65.00°	Non	Reflex	395.00	359.90°	-64.30°	Non
Reflex	299.00	358.50°	-65.00°	Non	Reflex	398.00	0.10°	-64.30°	Non
Reflex	302.00	358.90°	-64.90°	Non	Reflex	401.00	359.70°	-64.00°	Non
Reflex	305.00	359.00°	-64.90°	Non	Reflex	404.00	360.00°	-64.20°	Non
Reflex	308.00	358.90°	-64.80°	Non	Reflex	407.00	0.00°	-64.10°	Non
Reflex	311.00	357.80°	-64.70°	Non	Reflex	410.00	359.40°	-64.10°	Non
Reflex	314.00	0.50°	-64.60°	Non	Reflex	413.00	359.10°	-64.00°	Non
Reflex	317.00	360.00°	-64.60°	Non	Reflex	416.00	356.20°	-64.10°	Non
Reflex	320.00	0.70°	-64.60°	Non	Reflex	419.00	359.90°	-64.10°	Non
Reflex	323.00	1.00°	-64.60°	Non	Reflex	422.00	2.30°	-64.10°	Non
Reflex	326.00	0.60°	-64.60°	Non	Reflex	425.00	2.30°	-64.10°	Non
Reflex	329.00	2.70°	-64.40°	Oui	Reflex	428.00	1.50°	-64.00°	Non
Reflex	332.00	359.90°	-64.40°	Non	Reflex	431.00	357.40°	-64.00°	Oui
Reflex	335.00	1.00°	-64.40°	Non					
Reflex	338.00	1.30°	-64.40°	Non					
Reflex	341.00	1.00°	-64.30°	Non					
Reflex	344.00	357.00°	-55.50°	Non					
Reflex	347.00	0.90°	-64.30°	Non					
Reflex	350.00	1.80°	-64.40°	Non					
Reflex	353.00	1.50°	-64.40°	Non					
Reflex	356.00	2.30°	-64.30°	Non					
Reflex	359.00	2.40°	-64.40°	Non					
Reflex	362.00	2.30°	-64.30°	Non					
Reflex	365.00	2.20°	-64.30°	Non					
Reflex	368.00	2.40°	-64.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	12.00	MT <b>Mort-terrain</b> Casing							
9.10	10.90	SR <b>Séricitique</b> Moderate, pervasive sericite alteration. Chl alteration.	9.10	10.90	D039885	1.80	1.255		1.255
10.90	44.82	HM <b>Hématisé</b> Moderate, pervasive hematite alteration. Localized patches of chl and sericite alteration. Localized oxidation.	10.90	12.30	D039886	1.40	0.018		0.018
12.00	113.00	SY; POR <b>Syérite; Porphyrique</b> Pink-red to purple porphyritic syenite. Pervasive hematite alteration, localized chl and sericite alteration forming network of mm seams. Localized and patchy, weak to moderate magnetism, mm seams of spec hematite as well as disseminated grains. Seams black, prismatic tourmaline, mm. Localized oxidation. Localized patches of silicification and blue-grey discolouration. Localized brecciation in areas of chl-sericite as well as silica-carbonate flooding, resulting syenite inclusions are angular to sub-rounded and mm up to 7cm. Trace up to 5% phenocrysts, subhedral, pale beige-grey, locally green and pink resulting from chl and hematite alteration, generally 0.5 to 1cm. Trace up to 1-2% py.	12.30	14.00	D039887	1.70	<0.005		0.001
			14.00	15.00	D039888	1.00	0.005		0.005
			15.00	16.60	D039889	1.60	0.496		0.496
			16.60	18.30	D039891	1.70	0.181		0.181
			18.30	20.00	D039892	1.70	<0.005		0.001
			20.00	21.50	D039894	1.50	0.084		0.084
			21.50	23.00	D039895	1.50	0.007		0.007
			23.00	24.50	D039896	1.50	0.068		0.068
			24.50	26.00	D039897	1.50	0.099		0.099
			26.00	27.00	D039898	1.00	0.272		0.272
			27.00	28.40	D039899	1.40	1.545		1.545
			28.40	29.70	D039900	1.30	0.797		0.797
			29.70	30.50	D039901	0.80	0.021		0.021
			30.50	32.00	D039902	1.50	0.120		0.120
			32.00	33.50	D039904	1.50	0.148		0.148
			33.50	35.00	D039905	1.50	0.263		0.263
			35.00	36.50	D039906	1.50	0.259		0.259
			36.50	38.00	D039907	1.50	0.291		0.291
			38.00	39.50	D039908	1.50	0.111		0.111
			39.50	41.00	D039909	1.50	0.067		0.067
			41.00	42.50	D039910	1.50	0.038		0.038
			42.50	44.00	D039911	1.50	0.019		0.019
			44.00	44.80	D039912	0.80	0.327		0.327
			44.80	46.00	D039914	1.20	2.260		2.260
44.82	52.70	SI	46.00	47.00	D039915	1.00	1.975		1.975

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
52.70	75.80	<b>Silicifié</b>	47.00	48.50	D039916	1.50	2.040		2.040
		Moderate, pervasive silicate alteration, blue-grey discolouration, sharp contacts, upper ~30 deg TCA and denoted by zone of brecciation, lower ~35 deg TCA. Weak chloritization.	48.50	50.00	D039917	1.50	3.130		3.130
			50.00	51.50	D039918	1.50	1.885		1.885
			51.50	52.70	D039919	1.20	1.335		1.335
		<b>HM</b>	52.70	54.40	D039920	1.70	0.517		0.517
		<b>Hématisé</b>	54.40	56.00	D039921	1.60	1.170		1.170
		Moderate, pervasive hematite alteration, weak to moderate magnetism. Localized chl and sericite alteration.	56.00	57.50	D039922	1.50	0.107		0.107
			57.50	58.30	D039924	0.80	0.009		0.009
			58.30	59.40	D039925	1.10	0.497		0.497
			59.40	60.50	D039926	1.10	<0.005		0.001
			60.50	62.00	D039927	1.50	0.019		0.019
			62.00	63.50	D039928	1.50	0.007		0.007
			63.50	65.00	D039929	1.50	0.065		0.065
			65.00	66.50	D039931	1.50	0.023		0.023
			66.50	68.00	D039932	1.50	<0.005		0.001
			68.00	69.50	D039934	1.50	0.163		0.163
			69.50	71.00	D039935	1.50	0.247		0.247
			71.00	72.50	D039936	1.50	0.121		0.121
			72.50	74.00	D039937	1.50	0.056		0.056
			74.00	75.00	D039938	1.00	0.155		0.155
	75.00	75.80	D039939	0.80	0.443		0.443		
75.80	76.80	<b>SI</b>	75.80	76.80	D039940	1.00	3.490		3.490
		<b>Silicifié</b>							
		Weak, pervasive silicification. Weak chl, sericite and hematite alteration.							
76.80	143.00	<b>HM</b>	76.80	78.50	D039941	1.70	0.300		0.300
		<b>Hématisé</b>	78.50	80.00	D039942	1.50	0.042		0.042
		Moderate to strong, pervasive hematite alteration, weak to moderate magnetism. Localized chl and sericite alteration.	80.00	81.50	D039944	1.50	0.041		0.041
			81.50	83.00	D039945	1.50	<0.005		0.001
			83.00	84.50	D039946	1.50	<0.005		0.001
			84.50	86.00	D039947	1.50	<0.005		0.001
			86.00	87.70	D039948	1.70	<0.005		0.001
			87.70	88.50	D039949	0.80	0.205		0.205
	88.50	89.50	D039950	1.00	0.014		0.014		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
113.00	380.00	SY; POR <b>Syénite; Porphyrique</b> Deep reddish-purple to red porphyritic syenite. Strong pervasive hematite alteration, moderate pervasive magnetism (strongest in areas of purple discolouration). Chl and sericite alteration (networks of seams), often creating mottled texture. 2-10% phenocrysts, pale grey-beige, often with green and/or pink discolouration, alteration rims, generally 2-5mm, up to ~1.5cm, subhedral with no specific orientation. Moderate degree of qtz-carb veins, irregular and oriented, pink to orange discolouration, up to ~10cm. Irregular, mm, seams of chl. Dispersed grain of spec hem. Traces of tourmaline. Localized patches of brecciation. Traces up to 1-2% of py.	89.50	90.30	D039951	0.80	<0.005		0.001
			90.30	92.00	D039952	1.70	<0.005		0.001
			92.00	93.50	D039954	1.50	<0.005		0.001
			93.50	95.00	D039955	1.50	<0.005		0.001
			95.00	96.40	D039956	1.40	<0.005		0.001
			96.40	98.00	D039957	1.60	<0.005		0.001
			98.00	99.50	D039958	1.50	<0.005		0.001
			99.50	101.00	D039959	1.50	<0.005		0.001
			101.00	102.50	D039960	1.50	<0.005		0.001
			102.50	104.00	D039961	1.50	<0.005		0.001
			104.00	105.50	D039962	1.50	<0.005		0.001
			105.50	107.00	D039964	1.50	<0.005		0.001
			107.00	108.50	D039965	1.50	<0.005		0.001
			108.50	110.00	D039966	1.50	<0.005		0.001
			110.00	111.00	D039967	1.00	<0.005		0.001
			111.00	112.00	D039968	1.00	<0.005		0.001
			112.00	113.00	D039969	1.00	<0.005		0.001
			113.00	114.50	D039970	1.50	<0.005		0.001
			114.50	116.00	D039971	1.50	<0.005		0.001
			116.00	117.50	D039972	1.50	<0.005		0.001
116.56	116.60	V ca;4 cm;;;50°; <b>Veine de calcite 4 cm 50°</b> White-beige qtz-carb vein, brecciated, angular clasts of syenite up to 1.5cm.	117.50	119.00	D039974	1.50	<0.005		0.001
			119.00	120.50	D039975	1.50	<0.005		0.001
			120.50	122.00	D039976	1.50	<0.005		0.001
121.40	121.65	V ca;23 cm;;;; <b>Veine de calcite 23 cm</b> Irregular vein of qtz-carb mottled with chl and hematite alteration.	122.00	123.50	D039977	1.50	<0.005		0.001
			123.50	125.00	D039978	1.50	<0.005		0.001
			125.00	126.50	D039979	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			126.50	128.00	D039980	1.50	<0.005		0.001
			128.00	129.50	D039981	1.50	<0.005		0.001
			129.50	131.00	D039982	1.50	<0.005		0.001
			131.00	132.50	D039984	1.50	<0.005		0.001
			132.50	134.00	D039985	1.50	<0.005		0.001
			134.00	135.50	D039986	1.50	<0.005		0.001
			135.50	137.00	D039987	1.50	<0.005		0.001
			137.00	138.50	D039988	1.50	<0.005		0.001
137.55	137.68	V ca;7 cm;;;30°;; <b>Veine de calcite 7 cm 30°</b> Pink-red qtz-carb vein with patches of yellow-orange discolouration. Slightly sheared and surrounded by ~1-2cm of sheared chl-sericite, mm, seams.	138.50	140.20	D039989	1.70	<0.005		0.001
			140.20	141.00	D039991	0.80	0.069		0.069
			141.00	142.10	D039992	1.10	<0.005		0.001
			142.10	143.00	D039994	0.90	<0.005		0.001
142.35	142.61	V ca;3 cm;;;;; <b>Veine de calcite 3 cm</b> Grey qtz carb vein, brecciated angular syenite frags up to 3cm.							
143.00	244.30	CB03 <b>Carbonaté 3</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	143.00	144.50	D039995	1.50	<0.005		0.001
			144.50	146.00	D039996	1.50	0.104		0.104
144.84	144.94	V ca;6 cm;;;;; <b>Veine de calcite 6 cm</b> white to pink qtz-carb vein, chl rimmed, inclusions of hematite.	146.00	147.50	D039997	1.50	<0.005		0.001
			147.50	149.00	D039998	1.50	<0.005		0.001
			149.00	150.50	D039999	1.50	<0.005		0.001
			150.50	152.00	D040000	1.50	0.008		0.008
			152.00	153.40	D040001	1.40	<0.005		0.001
			153.40	155.00	D040002	1.60	<0.005		0.001
			155.00	156.50	D040004	1.50	<0.005		0.001
			156.50	158.00	D040005	1.50	<0.005		0.001
			158.00	159.50	D040006	1.50	<0.005		0.001
159.16	159.20	V ca;3 cm;;;50°;; <b>Veine de calcite 3 cm 50°</b> Yellowish-white qtz-carb vein, inclusions of hematite alteration, seams of conc chl.	159.50	161.00	D040007	1.50	<0.005		0.001
			161.00	162.50	D040008	1.50	<0.005		0.001
			162.50	164.00	D040009	1.50	0.014		0.014
			164.00	165.50	D040010	1.50	0.019		0.019
			165.50	167.00	D040011	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
169.22	169.25	V ca;3 cm;;70°; <b>Veine de calcite 3 cm 70°</b> White qtz-carb vein, hem and chl inclusions.	167.00	168.50	D040012	1.50	<0.005		0.001
			168.50	170.00	D040014	1.50	0.005		0.005
			170.00	171.60	D040015	1.60	<0.005		0.001
171.14	171.53	V ca;::::; <b>Veine de calcite</b> Zone of irregular qtz-carb veins, pink to red discolouration, sub parallel TCA, mild brecciation.	171.60	173.00	D040016	1.40	<0.005		0.001
			173.00	174.50	D040017	1.50	0.007		0.007
			174.50	176.00	D040018	1.50	<0.005		0.001
174.92	175.04	V ca;::;30°; <b>Veine de calcite 30°</b> Cluster of white qtz-carb veins, rimmed with hematite alteration (pink discolouration), inclusions of conc chl.							
175.27	175.31	V ca;4 cm;;30°; <b>Veine de calcite 4 cm 30°</b> White qtz-carb vein, rimmed with hematite alteration (pink discolouration), inclusions of conc chl.	176.00	177.50	D040019	1.50	<0.005		0.001
176.09	176.17	V ca;8 cm;;70°; <b>Veine de calcite 8 cm 70°</b> White-purple/grey qtz carb vein, hematite alteration and inclusions of conc chl.	177.50	179.00	D040020	1.50	<0.005		0.001
			179.00	180.60	D040021	1.60	<0.005		0.001
			180.60	182.00	D040022	1.40	<0.005		0.001
			182.00	183.50	D040024	1.50	<0.005		0.001
			183.50	185.10	D040025	1.60	0.007		0.007
184.40	184.48	V ca;8 cm;;35°; <b>Veine de calcite 8 cm 35°</b> White-grey qtz carb vein, hematite alteration and conc inclusions of chl, ~35-60 deg TCA.							
184.52	184.56	V ca;4 cm;;35°; <b>Veine de calcite 4 cm 35°</b> White-grey qtz carb vein, hematite alteration and conc inclusions of ch.							
184.87	185.10	V ca;9 cm;;40°; <b>Veine de calcite 9 cm 40°</b> White-grey qtz carb vein, conc inclusions of chl.	185.10	186.50	D040026	1.40	<0.005		0.001
			186.50	188.00	D040027	1.50	<0.005		0.001
			188.00	189.50	D040028	1.50	<0.005		0.001
			189.50	191.00	D040029	1.50	<0.005		0.001
190.55	190.59	V ca;4 cm;;80°; <b>Veine de calcite 4 cm 80°</b> Pink qtz-carb vein.	191.00	192.50	D040031	1.50	<0.005		0.001
			192.50	194.00	D040032	1.50	<0.005		0.001
			194.00	195.50	D040034	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
198.91	198.98	V ca;6 cm;;;30°; <b>Veine de calcite 6 cm 30°</b> Mottled pink-grey qtz-carb vein, hematite alteration, inclusions of conc chl, inclusions of conc spec hem.	195.50	197.00	D040035	1.50	<0.005		0.001
			197.00	198.50	D040036	1.50	<0.005		0.001
			198.50	199.40	D040037	0.90	<0.005		0.001
			199.40	200.20	D040038	0.80	<0.005		0.001
			200.20	201.50	D040039	1.30	<0.005		0.001
			201.50	203.00	D040040	1.50	<0.005		0.001
			203.00	204.50	D040041	1.50	<0.005		0.001
			204.50	206.00	D040042	1.50	<0.005		0.001
			206.00	207.50	D040044	1.50	<0.005		0.001
			207.50	209.00	D040045	1.50	<0.005		0.001
211.06	211.13	V ca;7 cm;;;65°; <b>Veine de calcite 7 cm 65°</b> White-grey qtz carb vein, hematite alteration (local pink discolouration), inclusions of conc chl, 55 to 65 deg TCA.	209.00	210.50	D040046	1.50	<0.005		0.001
			210.50	212.00	D040047	1.50	<0.005		0.001
			212.00	213.50	D040048	1.50	<0.005		0.001
			213.50	215.00	D040049	1.50	<0.005		0.001
			215.00	216.50	D040050	1.50	<0.005		0.001
			216.50	218.00	D040051	1.50	<0.005		0.001
			218.00	219.50	D040052	1.50	<0.005		0.001
			219.50	221.00	D040054	1.50	<0.005		0.001
221.11	221.54	V ca;4 cm;;;;; <b>Veine de calcite 4 cm</b> White-grey, irregular qtz-carb vein, sub parallel TCA, local brecciation.	221.00	222.50	D040055	1.50	0.014		0.014
			222.50	224.00	D040056	1.50	<0.005		0.001
			224.00	225.50	D040057	1.50	<0.005		0.001
			225.50	227.00	D040058	1.50	<0.005		0.001
226.78	226.93	V ca;3 cm;;;;; <b>Veine de calcite 3 cm</b> White-pink-grey qtz-carb vein, irregular, sub-parallel TCA, local hematite alteration, inclusions of conc chl.	227.00	228.50	D040059	1.50	<0.005		0.001
			228.50	230.00	D040060	1.50	<0.005		0.001
			230.00	231.50	D040061	1.50	<0.005		0.001
			231.50	233.10	D040062	1.60	<0.005		0.001
			233.10	234.50	D040064	1.40	<0.005		0.001
233.16	233.41	V ca;;;;; <b>Veine de calcite</b> Zone of brecciation. Pale white-grey qtz-carb matrix with angular syenite clasts up to 4cm, local hematite alteration, chl rimmed. 2.5cm band of pale green, bleached, sericite-chl altered syenite.	234.50	236.00	D040065	1.50	<0.005		0.001
			236.00	237.50	D040066	1.50	0.007		0.007
			237.50	238.90	D040067	1.40	<0.005		0.001
238.90	240.50	D040068	1.60	0.565		0.565			

Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
243.00	245.20	Zone of qtz-carb flooding and brecciation. Sericite and chl altered.  V ca;3 cm;30°; <b>Veine de calcite 30°</b> Zone of sericite-chl flooding, sheared ~30 deg TCA, local brecciation, 12cm qtz carb vein with hematite, sericite and chl alteration.	240.50	242.00	D040069	1.50	0.021		0.021		
			242.00	243.00	D040070	1.00	<0.005		0.001		
			243.00	244.30	D040071	1.30	0.481		0.481		
244.30	245.20	SR <b>Séricitique</b> Moderate pervasive sericite alteration. Chl alteration.	244.30	245.20	D040072	0.90	0.309		0.309		
245.20	246.50	HM <b>Hématisé</b> Strong pervasive hematite alteration. Chl alteration. Weak carbonate alteration through abundant stringers.	245.20	246.50	D040074	1.30	<0.005		0.001		
246.50	270.10	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	246.50	248.00	D040075	1.50	<0.005		0.001		
			248.00	249.50	D040076	1.50	<0.005		0.001		
			249.50	251.00	D040077	1.50	<0.005		0.001		
			251.00	252.50	D040078	1.50	<0.005		0.001		
			252.50	254.00	D040079	1.50	<0.005		0.001		
			254.00	255.50	D040080	1.50	<0.005		0.001		
			255.50	257.00	D040081	1.50	<0.005		0.001		
			257.00	258.50	D040082	1.50	<0.005		0.001		
			258.50	260.00	D040084	1.50	<0.005		0.001		
			260.00	261.50	D040085	1.50	<0.005		0.001		
264.96	264.99	V ca;3 cm;70°; <b>Veine de calcite 3 cm 70°</b> White-grey qtz carb vein, hematite alteration, conc chl inclusions.	261.50	263.00	D040086	1.50	<0.005		0.001		
			263.00	264.50	D040087	1.50	0.025		0.025		
			264.50	266.00	D040088	1.50	0.011		0.011		
			266.00	267.50	D040089	1.50	0.109		0.109		
			267.50	269.00	D040091	1.50	0.091		0.091		
			269.00	270.10	D040092	1.10	0.059		0.059		
			270.10	272.00	SI <b>Silicifié</b> Weak to moderate, pervasive silicification.						
			270.10	272.00	V ca;3 cm;70°; <b>Veine de calcite</b> Zone of silicification and brecciation, irregular, mm qtz-carb	270.10	271.00	D040094	0.90	2.610	
271.00	272.00	D040095				1.00	3.040		3.040		

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
272.00	273.50	veins. HM; HM <b>Hématisé; Hématisé</b> Strong pervasive hematite alteration. Chl alteration (network of stringers).	272.00	273.50	D040096	1.50	0.038		0.038
273.50	288.70	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	273.50	275.00	D040097	1.50	0.059		0.059
			275.00	276.30	D040098	1.30	0.036		0.036
			276.30	278.00	D040099	1.70	<0.005		0.001
			278.00	279.50	D040100	1.50	<0.005		0.001
			279.50	281.00	D040101	1.50	<0.005		0.001
			281.00	282.50	D040102	1.50	<0.005		0.001
			282.50	284.00	D040104	1.50	<0.005		0.001
			284.00	285.50	D040105	1.50	<0.005		0.001
			285.50	287.00	D040106	1.50	<0.005		0.001
287.00	287.13	V ca;3 cm;;40°; <b>Veine de calcite 3 cm 40°</b> Pink-yellow qtz-carb vein with ~3cm accumulate of chl seams with trace tourmaline.	287.00	288.70	D040107	1.70	<0.005		0.001
288.70	293.00	HM <b>Hématisé</b> Strong pervasive hematite alteration, purple to red coloured syenite. Chl alteration through network of stringers. Local carbonate alteration.	288.70	290.00	D040108	1.30	<0.005		0.001
288.80	288.88	V ca;;;40°; <b>Veine de calcite 40°</b> Pink qtz-carb veins alternating between chl rich bands.	290.00	291.50	D040109	1.50	<0.005		0.001
			291.50	293.00	D040110	1.50	<0.005		0.001
291.82	292.00	V ca;;;;; <b>Veine de calcite</b> Zone of brecciation, blue-white qtz-carb matrix with angular clasts of green-red syenite up to 2.5cm.							
293.00	336.40	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	293.00	294.00	D040111	1.00	<0.005		0.001
			294.00	295.00	D040112	1.00	<0.005		0.001
			295.00	296.00	D040114	1.00	<0.005		0.001
295.10	295.64	V ca;5 cm;;;;; <b>Veine de calcite 5 cm</b> Large (entre core) pink-grey qtz carb vein, sub parallel TCA,	296.00	297.50	D040115	1.50	0.037		0.037

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
296.06	296.43	surrounded by banding of conc chl-sericite seams. V ca;;;40°; <b>Veine de calcite 40°</b> Zone of abundant, sheared sericite-chl seams.						
296.53	296.82	V ca;;;;; <b>Veine de calcite</b> Zone of brecciation, pink qtz-carb matrix with sub-angular to rounded clasts of red syenite, up to 1cm.	297.50	298.70	D040116	1.20	0.018	0.018
			298.70	300.20	D040117	1.50	0.016	0.016
299.00	299.34	V ca;;;30°; <b>Veine de calcite 30°</b> Zone of chl-sericite rich bands followed by zone of brecciation, pinky-orange qtz-carb matrix with sub-angular red syenite clasts and conc seams of py.	300.20	301.70	D040118	1.50	<0.005	0.001
			301.70	303.40	D040119	1.70	0.027	0.027
			303.40	305.00	D040120	1.60	<0.005	0.001
			305.00	306.50	D040121	1.50	<0.005	0.001
			306.50	308.00	D040122	1.50	<0.005	0.001
			308.00	309.40	D040124	1.40	0.008	0.008
309.40	310.30	V ca;;;20°; <b>Veine de calcite 20°</b> Zone of brecciation. Dark green chloritic matrix with angular inclusions of red syenite up to 2cm. Weak carbonate alteration, minimal visible carbonate veins.	309.40	310.30	D040125	0.90	0.033	0.033
			310.30	311.10	D040126	0.80	0.773	0.773
			311.10	312.40	D040127	1.30	0.066	0.066
			312.40	314.00	D040128	1.60	0.018	0.018
			314.00	315.00	D040129	1.00	<0.005	0.001
			315.00	316.00	D040131	1.00	0.006	0.006
			316.00	317.00	D040132	1.00	0.547	0.547
316.82	316.87	V ca;;;50°; <b>Veine de calcite 50°</b> Gre-white qtz carb vein, minimal brecciation, hematite alteration, conc chl inclusions, conc py clusters.						
316.87	322.50	V ca;;;;; <b>Veine de calcite</b> Zone of increased brecciation. Patchy brecciation within dark green chloritic to blue-grey silicic-carbonate matrices.	317.00	318.50	D040134	1.50	0.078	0.078
			318.50	320.00	D040135	1.50	0.008	0.008
			320.00	321.50	D040136	1.50	0.008	0.008
			321.50	323.00	D040137	1.50	0.007	0.007
			323.00	324.50	D040138	1.50	0.006	0.006
			324.50	325.90	D040139	1.40	<0.005	0.001
			325.90	327.00	D040140	1.10	0.006	0.006
			327.00	327.80	D040141	0.80	<0.005	0.001
			327.80	329.00	D040142	1.20	<0.005	0.001
			329.00	330.60	D040144	1.60	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			330.60	332.00	D040145	1.40		<0.005		0.001
			332.00	333.50	D040146	1.50		<0.005		0.001
			333.50	334.90	D040147	1.40		<0.005		0.001
			334.90	336.40	D040148	1.50		<0.005		0.001
334.91	334.99	V ca;6 cm;;;30°; <b>Veine de calcite 6 cm 30°</b> Pink-white qtz-carb vein, 30-40 deg TCA, hematite alteration, conc seams and inclusions of chl up to 2cm thick.								
335.29	335.33	V ca;4 cm;;;25°; <b>Veine de calcite 4 cm 25°</b> Pink-white qtz-carb vein, hematite rimmed, incl of conc chl. 25-30 deg TCA.								
335.55	335.65	V ca;4 cm;;;25°; <b>Veine de calcite 4 cm 25°</b> Pink-white qtz-carb vein, hematite rimmed, incl of conc chl along interior. 25-30 deg TCA.								
335.96	336.07	V ca;8 cm;;;25°; <b>Veine de calcite 8 cm 25°</b> Pink-white qtz carb vein, hematite alteration, incl of conc chl, incl of conc tourmaline (black, prismatic, growth perpendicular to vein wall). 25-40 deg TCA.								
336.13	336.19	V ca;5 cm;;;20°; <b>Veine de calcite 5 cm 20°</b> White-pink qtz carb vein, hematite alteration, incl of conc chl, incl of tourmaline, traces of molybdenite. 20 to 30 deg TCA.								
336.40	338.10	HM <b>Hématisé</b> Strong pervasive hematite alteration, localized chl alteration. Weak carbonate alteration through network of veins.	336.40	338.10	D040149	1.70		<0.005		0.001
336.45	336.51	V ca;6 cm;;;60°; <b>Veine de calcite 6 cm 60°</b> White-pink qtz-carb vein, hematite alteration, incl of conc chl.								
336.71	336.82	V ca;3 cm;;;50°; <b>Veine de calcite 3 cm 50°</b> Patch of pink-white qtz carb veins, hematite alteration, incl of conc chl, traces of acicular tourmaline. ~50 deg TCA to irregular.								
337.02	337.05	V ca;3 cm;;;30°; <b>Veine de calcite 3 cm 30°</b> Vein of conc chl with inclusions of white qtz-carbonates.								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
337.13	337.18	V ca;3 cm;;;40°; <b>Veine de calcite 3 cm 40°</b> Vein of conc chl and white qtz-carbonates, local hematite alteration.							
337.25	337.28	V ca;3 cm;;;25°; <b>Veine de calcite 3 cm 25°</b> Vein of conc chl and white qtz-carbonates, local hematite alteration.							
337.96	338.01	V ca;5 cm;;;35°; <b>Veine de calcite 5 cm 35°</b> Pink-white qtz carb vein, hematite alteration, incl of conc chl, incl of tourmaline. 35 to 40 deg TCA.							
338.10	371.00	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	338.10	339.50	D040150	1.40	<0.005		0.001
			339.50	341.00	D040151	1.50	<0.005		0.001
			341.00	342.00	D040152	1.00	<0.005		0.001
			342.00	343.00	D040154	1.00	<0.005		0.001
343.00	344.33	V ca;;;;;; <b>Veine de calcite</b> Zone of brecciation, almost pervasive, blue-grey qtz carb matrix with angular clasts of green-red syenite up to 5cm.	343.00	344.70	D040155	1.70	0.006		0.006
344.40	344.70	V ca;;;;;; <b>Veine de calcite</b> Zone of brecciation, grey-white qtz-carb to dark green chloritic matrix, red-green angular clasts of syenite up to 4cm.	344.70	346.00	D040156	1.30	0.048		0.048
			346.00	347.00	D040157	1.00	0.030		0.030
			347.00	348.50	D040158	1.50	0.021		0.021
			348.50	350.00	D040159	1.50	0.005		0.005
			350.00	351.50	D040160	1.50	<0.005		0.001
			351.50	353.00	D040161	1.50	<0.005		0.001
			353.00	354.50	D040162	1.50	0.007		0.007
			354.50	356.00	D040164	1.50	<0.005		0.001
			356.00	357.50	D040165	1.50	<0.005		0.001
			357.50	359.00	D040166	1.50	0.088		0.088
362.87	362.95	V ca;8 cm;;;50°; <b>Veine de calcite 8 cm 50°</b> White-beige qtz-carb vein (1.5cm), surrounded by sericite-chl	359.00	360.50	D040167	1.50	<0.005		0.001
			360.50	362.00	D040168	1.50	<0.005		0.001
			362.00	363.50	D040169	1.50	<0.005		0.001
			363.50	365.00	D040170	1.50	0.121		0.121
			365.00	366.70	D040171	1.70	0.126		0.126
			366.70	368.00	D040172	1.30	0.087		0.087

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		and blue-grey qtz-carb banding, 50 to 60 deg TCA.	368.00	369.50	D040174	1.50		0.187	0.187
			369.50	371.00	D040175	1.50		0.214	0.214
369.64	370.12	V ca;::::; <b>Veine de calcite 30°</b> Zone of brecciation. Blue-grey qtz-carb matrix with angular, red-green-purple clasts of syenite.							
371.00	372.50	CH <b>Chloriteux</b> Strong pervasive chl and hematite alteration. Sericite alteration.	371.00	372.50	D040176	1.50		0.423	0.423
372.50	380.00	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive hematite alteration. Localized chl and sericite alteration.	372.50	374.00	D040177	1.50		0.030	0.030
			374.00	375.40	D040178	1.40		<0.005	0.001
375.40	375.54	V ca;::::; <b>Veine de calcite</b> Zone of brecciation. Pink-grey matrix with angular, purple clasts of syenite.	375.40	377.00	D040179	1.60		0.007	0.007
			377.00	377.90	D040180	0.90		<0.005	0.001
			377.90	379.00	D040181	1.10		<0.005	0.001
			379.00	380.00	D040182	1.00		<0.005	0.001
380.00	431.20	SY; POR <b>Syérite; Porphyrique</b> Altered syenite porphyry. Greenish to purple to reddish grey. Localized weak carbonate alteration. Localized weak silicification. Chl, hem and sericite alteration. Localized oxidation. Abundant qtz-carb seams, irregular as well as oriented, mm up to 10cm. Trace to 5% altered phenos, mm, subhedral, beige to green-orange. Localized brecciation. Weak to moderate pervasive magnetism. Interlayered with units of sheared (~30-55 deg TCA), bleached, chl-sericite-carbonate bands.	380.00	381.00	D040184	1.00		0.198	0.198
			381.00	382.00	D040185	1.00		0.047	0.047
			382.00	383.50	D040186	1.50		2.360	2.360
380.00	395.00	SR <b>Séricitique</b> Pervasive sericite, chl and hem alteration. Little carbonate alteration, patchy. Weak silicification.							
382.75	382.90	V ca;10 cm;;30°;; <b>Veine de calcite 10 cm 30°</b> White-grey qtz-carb vein, local yellow-orange discolouration, local hematite and chl alteration. 30 deg TCA to irregular.							
382.97	383.03	V ca;6 cm;;50°;; <b>Veine de calcite 6 cm 50°</b> White-grey qtz-carb vein, local yellow-orange discolouration,	383.50	384.60	D040187	1.10		0.289	0.289
			384.60	386.00	D040188	1.40		0.030	0.030



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		local hematite and chl alteration.	386.00	387.50	D040189	1.50	0.015		0.015
			387.50	388.80	D040191	1.30	0.046		0.046
			388.80	390.50	D040192	1.70	0.028		0.028
			390.50	392.00	D040194	1.50	0.024		0.024
			392.00	393.50	D040195	1.50	0.028		0.028
			393.50	395.00	D040196	1.50	0.118		0.118
395.00	409.00	CB	395.00	396.50	D040197	1.50	0.022		0.022
		<b>Carbonaté</b>	396.50	398.20	D040198	1.70	0.123		0.123
		Weak to moderate, pervasive carbonate alteration. Strong pervasive chl-sericite alteration. Localized weak hem alteration.	398.20	399.00	D040199	0.80	0.134		0.134
398.37	398.45	V ca;8 cm;;45°;;	399.00	400.10	D040200	1.10	0.122		0.122
		<b>Veine de calcite 8 cm 45°</b>	400.10	401.70	D040201	1.60	0.087		0.087
		Grey-white qtz carb vein, localized yellow discolouration, chl rimmed.	401.70	403.20	D040202	1.50	0.040		0.040
			403.20	404.00	D040204	0.80	0.302		0.302
			404.00	405.00	D040205	1.00	0.446		0.446
			405.00	406.00	D040206	1.00	0.022		0.022
			406.00	407.00	D040207	1.00	0.026		0.026
			407.00	407.90	D040208	0.90	0.028		0.028
			407.90	408.90	D040209	1.00	0.703		0.703
			408.90	410.30	D040210	1.40	0.238		0.238
409.00	410.30	SR							
		<b>Séricitique</b>							
		Pervasive sericite and chl alteration. Weak carbonate alteration.							
410.30	414.50	CB	410.30	411.40	D040211	1.10	0.007		0.007
		<b>Carbonaté</b>	411.40	412.90	D040212	1.50	<0.005		0.001
		Weak to moderate, pervasive carbonate alteration. Strong pervasive chl-sericite alteration. Localized weak hem alteration.	412.90	413.70	D040214	0.80	<0.005		0.001
			413.70	414.50	D040215	0.80	0.013		0.013
413.72	414.19	V ca;13 cm;;40°;;							
		<b>Veine de calcite 13 cm 40°</b>							
		Zone of sheared chl rich seams and qtz-carb veins. Localized yellow and pink discolouration. 40-60 deg TCA.							
414.50	416.00	HM	414.50	416.00	D040216	1.50	0.013		0.013
		<b>Hématisé</b>							
		Moderate pervasive hematite alteration. Network of chl alteration seams.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
416.00	420.00	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive chl-sericite alteration. Localized weak hem alteration.	416.00	416.80	D040217	0.80	0.034		0.034
			416.80	417.60	D040218	0.80	0.197		0.197
			417.60	419.10	D040219	1.50	0.068		0.068
			419.10	419.90	D040220	0.80	0.031		0.031
			419.90	420.90	D040221	1.00	0.103		0.103
420.00	421.00	SR <b>Séricitique</b> Sericite and chl alteration.	420.90	422.00	D040222	1.10	0.026		0.026
421.00	427.20	CB <b>Carbonaté</b> Weak to moderate, pervasive carbonate alteration. Strong pervasive chl-sericite alteration. Localized weak hem alteration.	422.00	423.50	D040224	1.50	0.643		0.643
			423.50	425.00	D040225	1.50	0.352		0.352
			425.00	426.50	D040226	1.50	0.187		0.187
			426.50	427.40	D040227	0.90	0.105		0.105
427.20	431.20	SR <b>Séricitique</b> Pervasive sericite and chl alteration.	427.40	429.00	D040228	1.60	0.140		0.140
			429.00	429.90	D040229	0.90	0.072		0.072
429.08	429.19	V ca;11 cm;;;5°;; <b>Veine de calcite 11 cm 5°</b> White qtz-carb vein with localized yellow-orange discolouration. 5 to 10 deg TCA.							
429.90	430.28	V ca;38 cm;;;25°;; <b>Veine de calcite 38 cm 25°</b> White qtz-carb vein, local yellow discolouration, incl of conc chl, conc clusters of py. 25-55 deg TCA.	429.90	431.20	D040231	1.30	0.333		0.333
431.20	Fin du sondage Nombre d'échantillons : 305 Nombre d'échantillons QAQC : 42 Longueur totale échantillonnée : 422.10								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
15.00	15.00	D039890	M1	0.00	0.006	0.006
18.30	18.30	D039893	J	0.00	0.802	0.802
30.50	32.00	D039903	D039902	1.50	0.110	0.110
44.00	44.00	D039913	K	0.00	1.075	1.075
56.00	57.50	D039923	D039922	1.50	0.114	0.114
63.50	63.50	D039930	M1	0.00	<0.005	0.001
66.50	66.50	D039933	L	0.00	2.180	2.180
78.50	80.00	D039943	D039942	1.50	0.038	0.038
90.30	90.30	D039953	M	0.00	2.970	2.970
104.00	105.50	D039963	D039962	1.50	<0.005	0.001
116.00	116.00	D039973	J	0.00	0.790	0.790
129.50	131.00	D039983	D039982	1.50	<0.005	0.001
138.50	138.50	D039990	M1	0.00	<0.005	0.001
141.00	141.00	D039993	K	0.00	1.080	1.080
153.40	155.00	D040003	D040002	1.60	<0.005	0.001
167.00	167.00	D040013	L	0.00	2.080	2.080
180.60	182.00	D040023	D040022	1.40	<0.005	0.001
189.50	189.50	D040030	M1	0.00	<0.005	0.001
192.50	192.50	D040033	M	0.00	3.100	3.100
204.50	206.00	D040043	D040042	1.50	<0.005	0.001
218.00	218.00	D040053	J	0.00	0.749	0.749
231.50	233.10	D040063	D040062	1.60	<0.005	0.001
244.30	244.30	D040073	K	0.00	0.973	0.973
257.00	258.50	D040083	D040082	1.50	<0.005	0.001
266.00	266.00	D040090	M1	0.00	<0.005	0.001
269.00	269.00	D040093	L	0.00	2.170	2.170
281.00	282.50	D040103	D040102	1.50	<0.005	0.001
294.00	294.00	D040113	M	0.00	2.850	2.850
306.50	308.00	D040123	D04122	1.50	<0.005	0.001
314.00	314.00	D040130	M1	0.00	<0.005	0.001
316.00	316.00	D040133	J	0.00	0.790	0.790
327.80	329.00	D040143	D040142	1.20	<0.005	0.001
341.00	341.00	D040153	K	0.00	0.950	0.950

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
353.00	354.50	D040163	D040162	1.50	0.005	0.005
366.70	366.70	D040173	L	0.00	2.150	2.150
379.00	380.00	D040183	D040182	1.00	<0.005	0.001
386.00	386.00	D040190	M1	0.00	<0.005	0.001
388.80	388.80	D040193	M	0.00	2.890	2.890
401.70	403.20	D040203	D040202	1.50	0.057	0.057
411.40	411.40	D040213	J	0.00	0.777	0.777
420.90	422.00	D040223	D040222	1.10	0.024	0.024
429.90	429.90	D040230	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-214</b>	Titre minier :	Section :	631000
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-05-07	Date de description :	2010-06-20
	Au : 2010-05-08		

Collet

Azimut : 0.00°  
 Plongée : -57.00°  
 Longueur : 140.90 m

UTM

Est	630 999.9
Nord	5 374 493.4
Élévation	298.5

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	0.00°	0.00°	Oui
Reflex	11.00	359.10°	-57.90°	Non
Reflex	14.00	0.30°	-58.10°	Non
Reflex	17.00	5.50°	-58.80°	Oui
Reflex	20.00	20.50°	-65.40°	Oui
Reflex	23.00	1.80°	-58.40°	Non
Reflex	26.00	2.50°	-57.90°	Non
Reflex	29.00	2.00°	-58.20°	Non
Reflex	32.00	2.50°	-58.30°	Non
Reflex	35.00	1.80°	-58.00°	Non
Reflex	38.00	1.20°	-57.40°	Non
Reflex	41.00	2.20°	-57.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	3.40°	-57.90°	Oui
Reflex	47.00	1.40°	-58.10°	Non
Reflex	50.00	2.50°	-57.80°	Non
Reflex	53.00	4.40°	-57.60°	Non
Reflex	56.00	4.80°	-58.10°	Non
Reflex	59.00	5.50°	-58.10°	Non
Reflex	62.00	4.20°	-58.10°	Non
Reflex	65.00	3.70°	-57.90°	Non
Reflex	68.00	3.50°	-57.90°	Non
Reflex	71.00	3.10°	-58.10°	Non
Reflex	74.00	3.20°	-58.10°	Non
Reflex	77.00	3.60°	-58.10°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	5.80°	-58.10°	Non					
Reflex	83.00	5.30°	-58.10°	Non					
Reflex	86.00	3.60°	-58.20°	Non					
Reflex	89.00	5.20°	-58.20°	Non					
Reflex	92.00	3.70°	-58.20°	Non					
Reflex	95.00	4.20°	-58.20°	Non					
Reflex	98.00	4.00°	-58.30°	Non					
Reflex	101.00	4.40°	-58.20°	Non					
Reflex	104.00	3.20°	-58.50°	Non					
Reflex	107.00	4.90°	-58.20°	Non					
Reflex	110.00	5.10°	-58.20°	Non					
Reflex	113.00	5.20°	-58.20°	Non					
Reflex	116.00	4.90°	-58.20°	Non					
Reflex	119.00	3.70°	-57.40°	Oui					
Reflex	122.00	4.30°	-58.00°	Non					
Reflex	125.00	4.40°	-58.00°	Non					
Reflex	128.00	4.50°	-58.20°	Non					
Reflex	131.00	4.80°	-57.80°	Non					
Reflex	134.00	4.70°	-57.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.00	MT						
		<b>Mort-terrain</b>						
2.00	108.70	SY; MAS; FIN	2.00	3.50	D027720	1.50	0.044	0.044
		<b>Syénite; Roche massive; Grains fins</b>	3.50	5.00	D027721	1.50	0.009	0.009
		massive, grenue, craquelures, localement altéré en calcite,	5.00	6.50	D027722	1.50	<0.005	0.001
		hématisation légère séricitation, oxydes de carbonâtes, veines	6.50	8.00	D027723	1.50	<0.005	0.001
		veinules de QZ carbonâté, PY fine irréd diss	8.00	9.50	D027724	1.50	0.047	0.047
			9.50	11.00	D027725	1.50	<0.005	0.001
			11.00	12.50	D027726	1.50	<0.005	0.001
			12.50	14.00	D027727	1.50	<0.005	0.001
			14.00	15.50	D027728	1.50	<0.005	0.001
			15.50	17.00	D027730	1.50	<0.005	0.001
			17.00	18.50	D027731	1.50	0.005	0.005
			18.50	20.00	D027732	1.50	<0.005	0.001
			20.00	21.50	D027733	1.50	<0.005	0.001
			21.50	23.00	D027734	1.50	<0.005	0.001
			23.00	24.50	D027735	1.50	0.013	0.013
			24.50	26.00	D027736	1.50	0.015	0.015
			26.00	27.50	D027737	1.50	0.016	0.016
			27.50	29.00	D027738	1.50	0.005	0.005
			29.00	30.00	D027740	1.00	0.005	0.005
			30.00	31.00	D027741	1.00	0.116	0.116
			31.00	32.50	D027742	1.50	0.016	0.016
			32.50	34.00	D027743	1.50	<0.005	0.001
			34.00	35.50	D027744	1.50	<0.005	0.001
			35.50	37.00	D027745	1.50	<0.005	0.001
			37.00	38.50	D027746	1.50	<0.005	0.001
			38.50	40.00	D027747	1.50	0.005	0.005
			40.00	41.50	D027748	1.50	<0.005	0.001
			41.50	43.00	D027750	1.50	<0.005	0.001
			43.00	44.50	D027751	1.50	<0.005	0.001
			44.50	46.00	D027752	1.50	<0.005	0.001
			46.00	47.50	D027753	1.50	<0.005	0.001
			47.50	49.00	D027754	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			49.00	50.50	D027755	1.50	<0.005		0.001
			50.50	52.00	D027757	1.50	<0.005		0.001
			52.00	53.50	D027758	1.50	<0.005		0.001
			53.50	55.00	D027760	1.50	<0.005		0.001
			55.00	56.50	D027761	1.50	0.008		0.008
			56.50	58.00	D027762	1.50	<0.005		0.001
			58.00	59.50	D027763	1.50	<0.005		0.001
			59.50	61.00	D027764	1.50	0.013		0.013
			61.00	62.50	D027765	1.50	<0.005		0.001
			62.50	64.00	D027766	1.50	<0.005		0.001
			64.00	65.50	D027767	1.50	0.006		0.006
			65.50	67.00	D027768	1.50	0.006		0.006
			67.00	68.50	D027770	1.50	<0.005		0.001
			68.50	70.00	D027771	1.50	0.012		0.012
			70.00	71.50	D027772	1.50	0.035		0.035
			71.50	73.00	D027773	1.50	0.024		0.024
			73.00	74.50	D027774	1.50	<0.005		0.001
			74.50	76.00	D027775	1.50	0.011		0.011
			76.00	77.50	D027776	1.50	<0.005		0.001
			77.50	79.00	D027777	1.50	0.016		0.016
			79.00	80.50	D027778	1.50	0.007		0.007
			80.50	82.00	D027780	1.50	0.016		0.016
2.00	56.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP sub automorphe ou arrondi,							
81.00	95.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux sub automorphe 0.2-0.6 cm, fortement hématisé, CL++, BO+	82.00	83.50	D027781	1.50	<0.005		0.001
			83.50	85.00	D027782	1.50	0.006		0.006
			85.00	86.50	D027783	1.50	0.019		0.019
			86.50	88.00	D027784	1.50	0.039		0.039
			88.00	89.50	D027785	1.50	0.013		0.013
			89.50	91.00	D027786	1.50	0.033		0.033
			91.00	92.50	D027787	1.50	0.028		0.028
			92.50	94.00	D027788	1.50	0.028		0.028
			94.00	95.00	D027790	1.00	0.079		0.079



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			95.00	96.50	D027791	1.50		0.140	
			96.50	98.00	D027792	1.50		0.091	
			98.00	99.50	D027793	1.50		0.025	
			99.50	101.00	D027794	1.50		0.014	
			101.00	102.00	D027795	1.00		0.032	
			102.00	103.50	D027797	1.50		0.037	
			103.50	105.00	D027798	1.50		0.010	
			105.00	106.20	D027800	1.20		0.011	
			106.20	107.20	D027801	1.00		0.072	
			107.20	108.70	D027802	1.50		1.310	
108.70	109.30	NR							
		<b>Carotte perdue</b>							
109.30	135.50	SY; MAS; FIN; MTY	109.30	111.00	D027803	1.70		0.008	0.008
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	111.00	112.50	D027804	1.50		0.009	0.009
		massive grenue altération en calcite, localement silicifié, passage	112.50	114.00	D027805	1.50		0.014	0.014
		légèrement cisailé pseudo foliations avec carbonâtes et séricite,	114.00	115.50	D027806	1.50		0.151	0.151
		hématisation chloritisation, biotite, oxydes de carbonâtes, calcite, PY	115.50	117.00	D027807	1.50		0.070	0.070
		fine irrég diss	117.00	118.50	D027808	1.50		0.274	0.274
			118.50	120.00	D027810	1.50		0.005	0.005
			120.00	121.50	D027811	1.50		<0.005	0.001
			121.50	123.00	D027812	1.50		0.093	0.093
122.00	123.00	FRC	123.00	124.60	D027813	1.60		0.411	0.411
		<b>Fracturé</b>	124.60	126.00	D027814	1.40		0.482	0.482
		fragments cm	126.00	127.50	D027815	1.50		0.050	0.050
			127.50	129.00	D027816	1.50		0.021	0.021
			129.00	130.50	D027817	1.50		0.044	0.044
130.50	132.00	SY; POR	130.50	132.00	D027818	1.50		0.530	0.530
		<b>Syénite; Porphyrique</b>	132.00	133.50	D027820	1.50		0.332	0.332
		phénocristaux de FP automorphe 0.3-0.7 cm, HM++, CL++, PY	133.50	134.50	D027821	1.00		0.007	0.007
		fine diss	134.50	135.50	D027822	1.00		<0.005	0.001
135.50	135.90	NR							
		<b>Carotte perdue</b>							
135.90	140.90	SY; MAS; FIN	135.90	137.50	D027823	1.60		<0.005	0.001
		<b>Syénite; Roche massive; Grains fins</b>	137.50	138.80	D027824	1.30		0.007	0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
138.80	140.00	FAI <b>Faille 70°</b> passage millonitisé avec qlq fragments de QZ et FP, boue verdâtre	138.80	140.90	D027825	2.10	0.082		0.082
140.90	Fin du sondage Nombre d'échantillons : 94 Nombre d'échantillons QAQC : 12 Longueur totale échantillonnée : 137.90								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	15.50	D027729	D027728	1.50	0.006	0.006
27.50	27.50	D027739	J	0.00	0.772	0.772
40.00	41.50	D027749	D027748	1.50	<0.005	0.001
49.00	49.00	D027756	M1	0.00	<0.005	0.001
52.00	52.00	D027759	K	0.00	1.080	1.080
65.50	67.00	D027769	D027768	1.50	<0.005	0.001
79.00	79.00	D027779	L	0.00	2.230	2.230
92.50	94.00	D027789	D027788	1.50	0.030	0.030
101.00	101.00	D027796	M1	0.00	<0.005	0.001
103.50	103.50	D027799	M	0.00	3.090	3.090
117.00	118.50	D027809	D027808	1.50	0.254	0.254
130.50	130.50	D027819	J	0.00	0.768	0.768

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-215</b>	Titre minier :	Section :	631100
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-05-08	Date de description :	2010-07-12
	Au : 2010-05-10		

Collet

Azimut : 0.00°  
 Plongée : -45.00°  
 Longueur : 260.00 m

UTM

Est	631 100.4
Nord	5 374 439.8
Élévation	312.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	8.00	0.00°	0.00°	Oui
Reflex	11.00	1.70°	-45.90°	Non
Reflex	14.00	4.30°	-45.60°	Oui
Reflex	17.00	2.10°	-45.40°	Non
Reflex	20.00	1.20°	-45.30°	Non
Reflex	23.00	0.10°	-45.30°	Non
Reflex	26.00	0.70°	-45.40°	Non
Reflex	29.00	2.20°	-45.50°	Oui
Reflex	32.00	0.80°	-45.40°	Non
Reflex	35.00	1.00°	-45.60°	Non
Reflex	38.00	1.70°	-45.70°	Non
Reflex	41.00	1.20°	-45.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	44.00	1.20°	-45.40°	Non
Reflex	47.00	1.60°	-45.30°	Non
Reflex	50.00	1.60°	-45.30°	Non
Reflex	53.00	1.90°	-45.40°	Non
Reflex	56.00	1.70°	-45.50°	Non
Reflex	59.00	2.00°	-45.50°	Non
Reflex	62.00	2.20°	-45.40°	Non
Reflex	65.00	2.30°	-45.40°	Non
Reflex	68.00	2.90°	-45.40°	Non
Reflex	71.00	2.70°	-45.30°	Non
Reflex	74.00	2.70°	-45.40°	Non
Reflex	77.00	2.90°	-45.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	80.00	2.90°	-45.40°	Non	Reflex	179.00	4.70°	-45.00°	Non
Reflex	83.00	2.90°	-45.30°	Non	Reflex	182.00	4.90°	-45.00°	Non
Reflex	86.00	2.80°	-45.30°	Non	Reflex	185.00	5.40°	-44.70°	Non
Reflex	89.00	2.80°	-45.30°	Non	Reflex	188.00	5.50°	-44.40°	Non
Reflex	92.00	2.80°	-45.40°	Non	Reflex	191.00	5.00°	-43.80°	Non
Reflex	95.00	2.70°	-45.20°	Non	Reflex	194.00	5.00°	-43.40°	Non
Reflex	98.00	2.80°	-45.20°	Non	Reflex	197.00	4.00°	-43.20°	Non
Reflex	101.00	2.60°	-45.20°	Non	Reflex	200.00	4.00°	-42.70°	Non
Reflex	104.00	2.80°	-45.30°	Non	Reflex	203.00	4.20°	-42.20°	Non
Reflex	107.00	2.60°	-45.30°	Non	Reflex	206.00	4.20°	-41.60°	Non
Reflex	110.00	2.70°	-45.20°	Non	Reflex	209.00	4.10°	-41.00°	Non
Reflex	113.00	2.60°	-45.20°	Non	Reflex	212.00	4.20°	-40.90°	Non
Reflex	116.00	2.50°	-45.20°	Non	Reflex	215.00	4.10°	-40.80°	Non
Reflex	119.00	2.60°	-45.20°	Non	Reflex	218.00	4.20°	-40.70°	Non
Reflex	122.00	2.70°	-45.20°	Non	Reflex	221.00	4.30°	-40.60°	Non
Reflex	125.00	2.70°	-45.20°	Non	Reflex	224.00	4.30°	-40.50°	Non
Reflex	128.00	2.70°	-45.20°	Non	Reflex	227.00	4.40°	-40.50°	Non
Reflex	131.00	2.50°	-45.20°	Non	Reflex	230.00	4.50°	-40.50°	Non
Reflex	134.00	2.50°	-45.00°	Non	Reflex	233.00	4.50°	-40.50°	Non
Reflex	137.00	2.70°	-45.00°	Non	Reflex	236.00	4.50°	-40.50°	Non
Reflex	140.00	2.70°	-45.00°	Non	Reflex	239.00	4.50°	-40.60°	Non
Reflex	143.00	2.80°	-45.00°	Non	Reflex	242.00	4.50°	-40.50°	Non
Reflex	146.00	2.90°	-45.00°	Non	Reflex	245.00	4.60°	-40.40°	Non
Reflex	149.00	3.00°	-45.00°	Non	Reflex	248.00	4.60°	-40.40°	Non
Reflex	152.00	3.10°	-45.00°	Non	Reflex	251.00	4.80°	-40.60°	Non
Reflex	155.00	3.30°	-45.00°	Non	Reflex	254.00	5.10°	-40.60°	Non
Reflex	158.00	3.40°	-45.10°	Non	Reflex	257.00	4.70°	-40.50°	Non
Reflex	161.00	3.50°	-45.00°	Non	Reflex	260.00	194.80°	-77.90°	Oui
Reflex	164.00	3.40°	-45.00°	Non					
Reflex	167.00	3.60°	-45.10°	Non					
Reflex	170.00	3.80°	-45.20°	Non					
Reflex	173.00	4.10°	-45.20°	Non					
Reflex	176.00	4.50°	-45.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.00	MT						
		<b>Mort-terrain</b>						
2.00	168.50	SY; MAS; FIN; MTY	2.00	3.50	D028718	1.50	0.044	0.044
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	3.50	5.00	D028719	1.50	0.010	0.010
		grenue, localement altéré en calcite, passages séricitisé, forte	5.00	6.50	D028720	1.50	0.009	0.009
		hématisation, cholrite, oxydes de carbonâtes, PY fine irrég diss	6.50	8.00	D028721	1.50	0.091	0.091
			8.00	9.50	D028722	1.50	0.065	0.065
			9.50	11.00	D028723	1.50	0.110	0.110
			11.00	12.50	D028724	1.50	0.089	0.089
			12.50	14.00	D028725	1.50	0.008	0.008
			14.00	15.50	D028727	1.50	0.116	0.116
			15.50	17.00	D028728	1.50	0.039	0.039
			17.00	18.50	D028729	1.50	<0.005	0.001
			18.50	20.00	D028730	1.50	0.009	0.009
			20.00	21.50	D028731	1.50	0.005	0.005
			21.50	23.00	D028732	1.50	0.007	0.007
			23.00	24.50	D028733	1.50	0.007	0.007
			24.50	26.00	D028734	1.50	0.377	0.377
			26.00	27.50	D028735	1.50	0.385	0.385
			27.50	29.00	D028737	1.50	0.102	0.102
			29.00	30.50	D028738	1.50	0.035	0.035
			30.50	32.00	D028739	1.50	<0.005	0.001
			32.00	33.50	D028740	1.50	0.010	0.010
			33.50	35.00	D028741	1.50	<0.005	0.001
			35.00	36.50	D028742	1.50	<0.005	0.001
			36.50	38.00	D028743	1.50	<0.005	0.001
			38.00	39.50	D028744	1.50	<0.005	0.001
			39.50	41.00	D028745	1.50	<0.005	0.001
			41.00	42.50	D028747	1.50	<0.005	0.001
			42.50	44.00	D028748	1.50	<0.005	0.001
			44.00	45.50	D028749	1.50	<0.005	0.001
			45.50	47.00	D028750	1.50	<0.005	0.001
			47.00	48.50	D028751	1.50	<0.005	0.001
			48.50	50.00	D028752	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.50	D028754	1.50	<0.005		0.001
	51.50	53.00	D028755	1.50	<0.005		0.001
	53.00	54.50	D028757	1.50	0.008		0.008
	54.50	56.00	D028758	1.50	<0.005		0.001
	56.00	57.50	D028759	1.50	<0.005		0.001
	57.50	59.00	D028760	1.50	<0.005		0.001
	59.00	60.50	D028761	1.50	0.019		0.019
	60.50	62.00	D028762	1.50	<0.005		0.001
	62.00	63.50	D028763	1.50	<0.005		0.001
	63.50	65.00	D028764	1.50	0.005		0.005
	65.00	66.50	D028765	1.50	<0.005		0.001
	66.50	68.00	D028767	1.50	<0.005		0.001
	68.00	69.50	D028768	1.50	<0.005		0.001
	69.50	71.00	D028769	1.50	<0.005		0.001
	71.00	72.50	D028770	1.50	<0.005		0.001
	72.50	74.00	D028771	1.50	<0.005		0.001
	74.00	75.50	D028772	1.50	0.009		0.009
	75.50	77.00	D028773	1.50	0.010		0.010
	77.00	78.50	D028774	1.50	<0.005		0.001
	78.50	80.00	D028775	1.50	0.241		0.241
	80.00	81.50	D028777	1.50	0.009		0.009
	81.50	83.00	D028778	1.50	<0.005		0.001
	83.00	84.50	D028779	1.50	0.016		0.016
	84.50	86.00	D028780	1.50	<0.005		0.001
	86.00	87.50	D028781	1.50	0.044		0.044
	87.50	89.00	D028782	1.50	0.005		0.005
	89.00	90.50	D028783	1.50	<0.005		0.001
	90.50	92.00	D028784	1.50	0.036		0.036
	92.00	93.50	D028785	1.50	<0.005		0.001
	93.50	95.00	D028787	1.50	<0.005		0.001
	95.00	96.50	D028788	1.50	<0.005		0.001
	96.50	98.00	D028789	1.50	0.299		0.299
	98.00	99.50	D028790	1.50	0.097		0.097

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			99.50	101.00	D028791	1.50	<0.005		0.001
			101.00	102.50	D028792	1.50	<0.005		0.001
			102.50	104.00	D028794	1.50	<0.005		0.001
			104.00	105.50	D028795	1.50	0.102		0.102
			105.50	107.00	D028797	1.50	0.051		0.051
			107.00	108.50	D028798	1.50	0.010		0.010
			108.50	110.00	D028799	1.50	0.011		0.011
			110.00	111.50	D028800	1.50	1.470		1.470
111.50	116.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux en lattes grossière 0.3-3 cm irrég diss, altération en calcite, CL++, SR++, PY fine	111.50	113.00	D028801	1.50	0.705		0.705
			113.00	114.50	D028802	1.50	2.700		2.700
			114.50	116.00	D028803	1.50	0.872		0.872
			116.00	117.50	D028804	1.50	0.037		0.037
			117.50	119.00	D028805	1.50	<0.005		0.001
			119.00	120.60	D028807	1.60	<0.005		0.001
120.60	122.00	CIS <b>Cisaillement</b> cisaillemnet 30-50° ac	120.60	122.00	D028808	1.40	0.062		0.062
			122.00	123.50	D028809	1.50	0.049		0.049
			123.50	125.00	D028810	1.50	0.017		0.017
			125.00	126.50	D028811	1.50	<0.005		0.001
			126.50	128.00	D028812	1.50	<0.005		0.001
			128.00	129.50	D028813	1.50	<0.005		0.001
			129.50	131.00	D028814	1.50	<0.005		0.001
			131.00	132.50	D028815	1.50	<0.005		0.001
			132.50	134.00	D028817	1.50	0.012		0.012
			134.00	135.50	D028818	1.50	<0.005		0.001
			135.50	137.00	D028819	1.50	<0.005		0.001
			137.00	138.50	D028820	1.50	<0.005		0.001
			138.50	140.00	D028821	1.50	<0.005		0.001
			140.00	141.50	D028822	1.50	<0.005		0.001
			141.50	143.00	D028823	1.50	<0.005		0.001
			143.00	144.00	D028824	1.00	<0.005		0.001
144.00	146.60	SY; BRI <b>Syénite; Brèche intrusive</b> brèche à fragments anguleux ou sub arrondi mm-cm, chlorite hématite							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
144.00	146.60	FRC <b>Fracturé</b> localament fragments cm	144.00	145.50	D028825	1.50	<0.005		0.001
			145.50	146.60	D028827	1.10	0.040		0.040
			146.60	148.00	D028828	1.40	0.472		0.472
			148.00	149.50	D028829	1.50	3.600		3.600
149.50	170.50	SI03; SR01; CB05 <b>Silicifié 3; Séricitique 1; Carbonaté 5</b> altération en calcite, PY fine diss	149.50	151.00	D028830	1.50	6.130		6.130
			151.00	152.50	D028831	1.50	3.040		3.040
			152.50	154.00	D028832	1.50	1.760		1.760
			154.00	155.50	D028834	1.50	1.590		1.590
			155.50	157.00	D028835	1.50	1.685		1.685
			157.00	158.50	D028837	1.50	1.620		1.620
			158.50	160.00	D028838	1.50	1.980		1.980
			160.00	161.50	D028839	1.50	1.735		1.735
			161.50	163.00	D028840	1.50	3.400		3.400
			163.00	164.50	D028841	1.50	2.040		2.040
			164.50	166.00	D028842	1.50	1.120		1.120
166.00	167.50	D028843	1.50	1.215		1.215			
167.50	168.50	D028844	1.00	1.755		1.755			
168.50	168.90	NR <b>Carotte perdue</b>							
168.90	172.80	SY; MTY; FIN <b>Syénite; Grains moyens; Grains fins</b>	168.90	170.50	D028845	1.60	1.775		1.775
			170.50	172.00	D028847	1.50	2.030		2.030
171.60	176.90	CIS <b>Cisaillement 40°</b>	172.00	172.80	D028848	0.80	3.010		3.010
172.80	173.80	GA; FIN; MAS <b>Gabbro 50°; Grains fins; Roche massive</b> Grenue, dykes mafique, altération en calcite et chlorite, veinules et veines carbonatés,	172.80	173.60	D028849	0.80	0.375		0.375
			173.60	175.00	D028850	1.40	0.013		0.013
173.80	176.90	SY; MTY; POR <b>Syénite 40°; Grains moyens; Porphyrique</b> altération en calcite, chloritisation, phénocristaux de FP sub automorphe localement orienté 40-60° ac, veines de QZ carbonatés	175.00	176.00	D028851	1.00	<0.005		0.001
			176.00	176.90	D028852	0.90	<0.005		0.001
176.90	211.10	GA; MAS; FIN <b>Gabbro 30°; Roche massive; Grains fins</b> grenue, localement phénocristaux de FP ou carbonates, altération en calcite et chlorite, veines et veinules carbonatés, PY fine diss	176.90	178.50	D028853	1.60	<0.005		0.001
			178.50	180.00	D028854	1.50	<0.005		0.001
			180.00	181.50	D028855	1.50	<0.005		0.001
			181.50	183.00	D028857	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			183.00	184.50	D028858	1.50	<0.005		0.001
			184.50	186.00	D028859	1.50	<0.005		0.001
			186.00	187.50	D028860	1.50	<0.005		0.001
			187.50	189.00	D028861	1.50	<0.005		0.001
			189.00	190.50	D028862	1.50	<0.005		0.001
			190.50	192.00	D028863	1.50	0.005		0.005
			192.00	193.50	D028864	1.50	<0.005		0.001
			193.50	195.00	D028865	1.50	<0.005		0.001
			195.00	196.50	D028867	1.50	<0.005		0.001
			196.50	198.00	D028868	1.50	<0.005		0.001
			198.00	199.50	D028869	1.50	<0.005		0.001
			199.50	201.00	D028870	1.50	<0.005		0.001
			201.00	202.50	D028871	1.50	<0.005		0.001
			202.50	204.00	D028872	1.50	0.007		0.007
			204.00	205.50	D028874	1.50	<0.005		0.001
			205.50	207.00	D028875	1.50	<0.005		0.001
			207.00	208.50	D028877	1.50	0.007		0.007
			208.50	210.00	D028878	1.50	<0.005		0.001
			210.00	211.10	D028879	1.10	<0.005		0.001
211.10	216.20	GR; FIN; MAS	211.10	212.50	D028880	1.40	<0.005		0.001
		<b>Grès 40°; Grains fins; Roche massive</b>	212.50	214.00	D028881	1.50	<0.005		0.001
		Localement, altération en calcite, veinules de carbonâtes, graphite, biotite, chlorite, PY fine	214.00	215.50	D028882	1.50	<0.005		0.001
			215.50	216.20	D028883	0.70	<0.005		0.001
216.20	228.00	BA; AMY; MAS	216.20	217.50	D028884	1.30	<0.005		0.001
		<b>Basalte 50°; Amygdalaire; Roche massive</b>	217.50	219.00	D028885	1.50	<0.005		0.001
		massive, altéré en calcite et carbonâtes, localement séricitisé, veines et veinules carbonaté, séricite	219.00	220.50	D028887	1.50	<0.005		0.001
			220.50	222.00	D028888	1.50	0.012		0.012
			222.00	223.50	D028889	1.50	<0.005		0.001
			223.50	225.00	D028890	1.50	<0.005		0.001
			225.00	226.50	D028891	1.50	<0.005		0.001
			226.50	228.00	D028892	1.50	<0.005		0.001
228.00	229.00	GR; MAS	228.00	229.10	D028893	1.10	0.005		0.005
		<b>Grès 40°; Roche massive</b>							
		massive altéré en calcite, lamination et séricitisation en fin d'éch,							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
228.00	228.30	passage de graphite, SR++, PY fine diss FRC <b>Fracturé 40°</b> fragments mêlés cm, boue verdâtre, CL+, BO++, PY fine							
229.00	251.70	BA; AMY <b>Basalte 30°; Amygdalaire</b> massive, amygdules de QZ et carbonâtes, altération en calcite, chlorite, séricite	229.10	230.50	D028894	1.40	<0.005		0.001
			230.50	232.00	D028895	1.50	<0.005		0.001
			232.00	233.50	D028897	1.50	<0.005		0.001
			233.50	235.00	D028898	1.50	<0.005		0.001
			235.00	236.50	D028899	1.50	<0.005		0.001
			236.50	238.00	D028900	1.50	<0.005		0.001
			238.00	239.50	D028901	1.50	<0.005		0.001
			239.50	241.00	D028902	1.50	<0.005		0.001
240.80	241.20	FRC <b>Fracturé 50°</b> fragments mêlés	241.00	242.50	D028903	1.50	<0.005		0.001
			242.50	244.00	D028904	1.50	<0.005		0.001
			244.00	245.50	D028905	1.50	<0.005		0.001
244.80	244.90	FAI <b>Faille 50°</b> fragments et boue verdâtre	245.50	247.00	D028907	1.50	<0.005		0.001
246.30	246.70	FAI <b>Faille 50°</b> zone de faille boue verdâtre fragmenté	247.00	248.50	D028908	1.50	<0.005		0.001
			248.50	250.00	D028909	1.50	<0.005		0.001
			250.00	251.70	D028910	1.70	<0.005		0.001
251.70	254.50	UM <b>Ultramaïfite serpentinisée 30°</b> massive aphanitique, induré, altération en calcite, sub bréchique, légère chloritisation, biotite, passage altéré en silice en fin d' éch, PY fine diss	251.70	253.00	D028911	1.30	<0.005		0.001
253.00	254.40	FRC <b>Fracturé 40°</b> fragments mm-cm	253.00	254.50	D028912	1.50	<0.005		0.001
254.50	260.00	GA; FIN <b>Gabbro 30°; Grains fins</b> grenue, altération en calcite et chlorite, carbonâtes, HM+, SR+, PY fine irrég diss	254.50	256.00	D028914	1.50	<0.005		0.001
			256.00	257.50	D028915	1.50	<0.005		0.001
			257.50	259.00	D028917	1.50	<0.005		0.001
			259.00	260.00	D028918	1.00	<0.005		0.001

## Corporation Minière Osisko Div. Exploration

260.00

Fin du sondage

Nombre d'échantillons : 176

Nombre d'échantillons QAQC : 25

Longueur totale échantillonnée : 257.60

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
12.50	14.00	D028726	D028725	1.50	0.010	0.010
26.00	26.00	D028736	J	0.00	0.745	0.745
39.50	41.00	D028746	D028745	1.50	0.005	0.005
48.50	48.50	D028753	M1	0.00	<0.005	0.001
51.50	51.50	D028756	K	0.00	1.140	1.140
65.00	66.50	D028766	D028765	1.50	<0.005	0.001
78.50	78.50	D028776	L	0.00	2.220	2.220
92.00	93.50	D028786	D028785	1.50	<0.005	0.001
101.00	101.00	D028793	M1	0.00	0.005	0.005
104.00	104.00	D028796	M	0.00	3.130	3.130
117.50	119.00	D028806	D028805	1.50	<0.005	0.001
131.00	131.00	D028816	J	0.00	0.725	0.725
144.00	145.50	D028826	D028825	1.50	<0.005	0.001
152.50	152.50	D028833	M1	0.00	0.008	0.008
155.50	155.50	D028836	K	0.00	1.065	1.065
168.90	170.50	D028846	D028845	1.60	1.780	1.780
180.00	180.00	D028856	L	0.00	2.120	2.120
193.50	195.00	D028866	D028865	1.50	<0.005	0.001
202.50	202.50	D028873	M1	0.00	<0.005	0.001
205.50	205.50	D028876	M	0.00	3.120	3.120
217.50	219.00	D028886	D028885	1.50	<0.005	0.001
230.50	230.50	D028896	J	0.00	0.765	0.765
244.00	245.50	D028906	D028905	1.50	<0.005	0.001
253.00	253.00	D028913	M1	0.00	<0.005	0.001
256.00	256.00	D028916	K	0.00	1.090	1.090

## Corporation Minière Osisko Div. Exploration

**Sondage :**        **BD10-216**

Titre minier :

Section :            631100

Canton :

Niveau :

Foré par :         Bradley

Rang :

Place de travail :    Malartic

Décrit par :       Johan Bergé

Lot :

Du :                2010-05-10

Date de description :

Au :                2010-05-12

Collet

UTM

Azimut :            0.00°  
Plongée :            -60.00°  
Longueur :         295.00 m

Est	631 100.5
Nord	5 374 439.1
Élévation	312.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	3.00	0.00°	0.00°	Oui
Reflex	6.00	359.30°	-58.80°	Non
Reflex	9.00	1.90°	-61.30°	Non
Reflex	12.00	0.50°	-60.00°	Non
Reflex	15.00	360.00°	-60.30°	Non
Reflex	18.00	359.80°	-60.40°	Non
Reflex	21.00	360.00°	-60.50°	Non
Reflex	24.00	0.10°	-60.50°	Non
Reflex	27.00	359.90°	-60.50°	Non
Reflex	30.00	360.00°	-60.50°	Non
Reflex	33.00	0.20°	-60.40°	Non
Reflex	36.00	0.30°	-60.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	39.00	0.30°	-60.40°	Non
Reflex	42.00	0.30°	-60.50°	Non
Reflex	45.00	359.80°	-60.60°	Non
Reflex	48.00	0.20°	-60.50°	Non
Reflex	51.00	1.20°	-60.50°	Non
Reflex	54.00	1.00°	-60.40°	Non
Reflex	57.00	1.40°	-60.30°	Non
Reflex	60.00	2.20°	-60.30°	Non
Reflex	63.00	2.30°	-60.50°	Non
Reflex	66.00	3.10°	-60.40°	Non
Reflex	69.00	1.40°	-60.50°	Non
Reflex	72.00	3.90°	-60.30°	Non

Description

\*Logged by Ciara Cooke from 54.5m.

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	75.00	4.80°	-60.40°	Non	Reflex	174.00	1.50°	-59.60°	Non
Reflex	78.00	3.10°	-60.30°	Non	Reflex	177.00	1.90°	-59.50°	Non
Reflex	81.00	1.70°	-60.30°	Non	Reflex	180.00	2.50°	-59.50°	Non
Reflex	84.00	1.20°	-60.30°	Non	Reflex	183.00	2.60°	-59.40°	Non
Reflex	87.00	12.90°	-60.30°	Oui	Reflex	186.00	3.80°	-59.40°	Non
Reflex	90.00	2.10°	-60.30°	Non	Reflex	189.00	3.70°	-59.40°	Non
Reflex	93.00	0.30°	-60.30°	Non	Reflex	192.00	3.90°	-59.30°	Non
Reflex	96.00	1.30°	-60.30°	Non	Reflex	195.00	2.40°	-59.30°	Non
Reflex	99.00	1.60°	-60.30°	Non	Reflex	198.00	3.80°	-59.30°	Non
Reflex	102.00	1.40°	-60.20°	Non	Reflex	201.00	4.80°	-59.20°	Non
Reflex	105.00	1.30°	-60.20°	Non	Reflex	204.00	4.20°	-59.10°	Non
Reflex	108.00	1.20°	-60.10°	Non	Reflex	207.00	2.40°	-59.10°	Non
Reflex	111.00	1.10°	-60.10°	Non	Reflex	210.00	2.40°	-59.10°	Non
Reflex	114.00	1.20°	-60.00°	Non	Reflex	213.00	2.90°	-59.00°	Non
Reflex	117.00	1.20°	-60.00°	Non	Reflex	216.00	3.20°	-58.90°	Non
Reflex	120.00	1.20°	-60.00°	Non	Reflex	219.00	3.80°	-59.00°	Non
Reflex	123.00	1.10°	-60.00°	Non	Reflex	222.00	4.40°	-59.00°	Non
Reflex	126.00	1.10°	-60.00°	Non	Reflex	225.00	4.20°	-58.90°	Non
Reflex	129.00	1.30°	-59.90°	Non	Reflex	228.00	4.20°	-58.90°	Non
Reflex	132.00	1.40°	-59.90°	Non	Reflex	231.00	4.50°	-59.00°	Non
Reflex	135.00	1.40°	-59.80°	Non	Reflex	234.00	4.60°	-59.00°	Non
Reflex	138.00	1.40°	-59.80°	Non	Reflex	237.00	5.10°	-58.90°	Non
Reflex	141.00	1.20°	-59.80°	Non	Reflex	240.00	5.00°	-58.90°	Non
Reflex	144.00	1.30°	-59.60°	Non	Reflex	243.00	4.90°	-58.90°	Non
Reflex	147.00	1.40°	-59.60°	Non	Reflex	246.00	5.40°	-58.90°	Non
Reflex	150.00	1.40°	-59.60°	Non	Reflex	249.00	5.60°	-58.90°	Non
Reflex	153.00	1.70°	-59.50°	Non	Reflex	252.00	5.30°	-58.80°	Non
Reflex	156.00	1.60°	-59.50°	Non	Reflex	255.00	5.70°	-58.90°	Non
Reflex	159.00	1.70°	-59.50°	Non	Reflex	258.00	5.70°	-58.80°	Non
Reflex	162.00	1.90°	-59.60°	Non	Reflex	261.00	5.60°	-58.70°	Non
Reflex	165.00	2.00°	-59.60°	Non	Reflex	264.00	5.60°	-58.70°	Non
Reflex	168.00	1.80°	-59.60°	Non	Reflex	267.00	5.60°	-58.80°	Non
Reflex	171.00	1.30°	-59.60°	Non	Reflex	270.00	6.20°	-58.80°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	273.00	5.90°	-58.80°	Non					
Reflex	276.00	5.90°	-58.60°	Non					
Reflex	279.00	6.00°	-58.50°	Non					
Reflex	282.00	6.30°	-58.60°	Non					
Reflex	285.00	6.40°	-58.50°	Non					
Reflex	288.00	6.60°	-58.50°	Non					
Reflex	291.00	6.60°	-58.50°	Non					
Reflex	294.00	6.90°	-58.40°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.30	MT <b>Mort-terrain</b> Pas de récupération.							
2.30	252.20	SY <b>Syénite</b> Syénite à grain fin avec phénocristaux de feldspath, dont la proportion varie dans l'unité. En général, altération hématitique= phénocristaux ; altération chloritique= peu de phénocristaux. Non magnétique en général, avec zone métrique magnétique (syénite hématisée plus sombre et riche en phénocristaux).  Red-purple syenite with green-yellow mottled alteration texture, locally pervasive green discolouration along with weak to moderate foliation. Localized chl and sericite alteration, pervasive chl-sericite seams. Localized carbonate alteration. Localized brecciated qtz-carb veins. Traces up to 7% phenocrysts, chl and hematite altered. Traces up to 1% py. Traces up to 5% specular hematite.	2.30	4.00	D039638	1.70	0.007		0.007
2.30	3.60	HM <b>Hématisé</b>							
3.60	11.10	CH <b>Chloriteux</b>	4.00	5.50	D039639	1.50	0.036		0.036
			5.50	7.00	D039640	1.50	0.360		0.360
			7.00	8.50	D039641	1.50	0.288		0.288
			8.50	10.00	D039642	1.50	0.199		0.199
8.60	8.80	QZVN <b>Veine de Quartz massive 40°</b> Veine de quartz dans syénite chloritisée. Rare cristaux de carbonates, légèrement ankéritisés.	10.00	11.30	D039644	1.30	0.020		0.020
11.10	17.10	HM <b>Hématisé</b>							
11.30	13.90	SY; BRI <b>Syénite; Brèche intrusive</b> Syénite bréchique. Clastes de syénite hématisés centimétriques dans une matrice de chlorite fine.	11.30	13.00	D039645	1.70	0.042		0.042
			13.00	14.00	D039646	1.00	0.017		0.017
			14.00	15.50	D039647	1.50	0.062		0.062
			15.50	17.00	D039648	1.50	0.012		0.012
			17.00	18.50	D039649	1.50	0.032		0.032
17.10	31.00	CH; HM <b>Chloriteux; Hématisé</b> Chloritisé, et hématisé dans une moindre mesure.	18.50	20.00	D039651	1.50	0.025		0.025
			20.00	21.50	D039652	1.50	0.043		0.043

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
27.10	27.30	QZVN <b>Veine de Quartz massive 40°</b> Veine de quartz dans syénite chloritisée.	21.50	23.00	D039654	1.50	0.018		0.018
			23.00	24.50	D039655	1.50	0.037		0.037
			24.50	26.00	D039656	1.50	0.133		0.133
			26.00	27.50	D039657	1.50	0.414		0.414
			27.50	29.00	D039658	1.50	0.064		0.064
			29.00	30.50	D039659	1.50	0.023		0.023
			30.50	32.00	D039660	1.50	0.325		0.325
31.00	46.70	HM; CH <b>Hématisé; Chloriteux</b> Hématisé, et chloritisé dans une moindre mesure.	32.00	33.50	D039661	1.50	0.035		0.035
			33.50	35.00	D039662	1.50	0.013		0.013
			35.00	36.50	D039664	1.50	0.052		0.052
			36.50	38.00	D039665	1.50	0.005		0.005
			38.00	39.50	D039666	1.50	0.005		0.005
			39.50	41.00	D039667	1.50	0.011		0.011
			41.00	42.50	D039668	1.50	<0.005		0.001
			42.50	44.00	D039669	1.50	0.023		0.023
			44.00	45.50	D039670	1.50	0.056		0.056
			45.50	47.00	D039671	1.50	<0.005		0.001
46.70	104.20	HM <b>Hématisé</b> Hématisé, avec rares passages décimétriques chloritisés.	47.00	48.50	D039672	1.50	0.124		0.124
			48.50	50.00	D039674	1.50	<0.005		0.001
49.00	58.00	SY; POR <b>Syénite; Porphyrique</b> Syénite avec une proportion de porphyroblastes importante (20%). Hématisée. Magnétique.	50.00	51.50	D039675	1.50	0.010		0.010
			51.50	53.00	D039676	1.50	<0.005		0.001
			53.00	54.50	D039677	1.50	0.011		0.011
			54.50	56.00	D039678	1.50	<0.005		0.001
			56.00	57.50	D039679	1.50	0.005		0.005
			57.50	59.00	D039680	1.50	<0.005		0.001
			59.00	60.50	D039681	1.50	<0.005		0.001
			60.50	62.00	D039682	1.50	<0.005		0.001
			62.00	63.50	D039684	1.50	<0.005		0.001
			63.50	65.00	D039685	1.50	0.006		0.006
65.00	66.50	D039686	1.50	0.019		0.019			
66.50	68.00	D039687	1.50	0.011		0.011			
68.00	69.50	D039688	1.50	0.005		0.005			

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			69.50	71.00	D039689	1.50	<0.005	0.001
			71.00	72.50	D039691	1.50	0.010	0.010
			72.50	74.00	D039692	1.50	0.013	0.013
			74.00	75.50	D039694	1.50	<0.005	0.001
			75.50	77.00	D039695	1.50	0.015	0.015
			77.00	78.50	D039696	1.50	0.141	0.141
			78.50	80.00	D039697	1.50	0.040	0.040
			80.00	81.50	D039698	1.50	0.026	0.026
			81.50	83.00	D039699	1.50	0.005	0.005
			83.00	84.50	D039700	1.50	0.009	0.009
			84.50	86.00	D039701	1.50	0.014	0.014
			86.00	87.50	D039702	1.50	0.006	0.006
			87.50	89.00	D039704	1.50	<0.005	0.001
			89.00	90.50	D039705	1.50	<0.005	0.001
			90.50	92.00	D039706	1.50	0.026	0.026
			92.00	93.50	D039707	1.50	0.500	0.500
			93.50	95.00	D039708	1.50	0.075	0.075
			95.00	96.00	D039709	1.00	<0.005	0.001
			96.00	96.50	D039710	0.50	0.030	0.030
			96.50	97.90	D039711	1.40	0.174	0.174
			97.90	99.60	D039712	1.70	0.137	0.137
			99.60	101.00	D039714	1.40	0.666	0.666
			101.00	102.40	D039715	1.40	0.265	0.265
			102.40	104.10	D039716	1.70	0.037	0.037
			104.10	105.50	D039717	1.40	0.406	0.406
104.20	108.10	CH	105.50	107.00	D039718	1.50	0.146	0.146
		<b>Chloriteux</b>	107.00	108.50	D039719	1.50	0.108	0.108
108.10	223.00	CB	108.50	110.00	D039720	1.50	0.005	0.005
		<b>Carbonaté</b>	110.00	111.50	D039721	1.50	1.115	1.115
		Moderate to strong, pervasive carbonate alteration.	111.50	113.00	D039722	1.50	0.124	0.124
			113.00	114.50	D039724	1.50	0.008	0.008
			114.50	116.00	D039725	1.50	0.302	0.302
			116.00	117.50	D039726	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	117.50	119.00	D039727	1.50	<0.005		0.001
	119.00	120.50	D039728	1.50	<0.005		0.001
	120.50	122.00	D039729	1.50	<0.005		0.001
	122.00	123.00	D039731	1.00	0.068		0.068
	123.00	124.00	D039732	1.00	<0.005		0.001
	124.00	125.00	D039734	1.00	<0.005		0.001
	125.00	126.50	D039735	1.50	<0.005		0.001
	126.50	128.00	D039736	1.50	<0.005		0.001
	128.00	129.50	D039737	1.50	<0.005		0.001
	129.50	131.00	D039738	1.50	0.007		0.007
	131.00	132.50	D039739	1.50	<0.005		0.001
	132.50	134.00	D039740	1.50	<0.005		0.001
	134.00	134.80	D039741	0.80	<0.005		0.001
	134.80	136.00	D039742	1.20	0.039		0.039
	136.00	137.00	D039744	1.00	<0.005		0.001
	137.00	138.00	D039745	1.00	<0.005		0.001
	138.00	139.00	D039746	1.00	0.153		0.153
	139.00	140.00	D039747	1.00	0.088		0.088
	140.00	141.50	D039748	1.50	0.061		0.061
	141.50	143.00	D039749	1.50	<0.005		0.001
	143.00	144.00	D039750	1.00	0.005		0.005
	144.00	145.40	D039751	1.40	0.596		0.596
	145.40	147.00	D039752	1.60	0.087		0.087
	147.00	148.00	D039754	1.00	<0.005		0.001
	148.00	149.50	D039755	1.50	<0.005		0.001
	149.50	151.20	D039756	1.70	0.611		0.611
	151.20	152.00	D039757	0.80	0.155		0.155
	152.00	153.50	D039758	1.50	0.033		0.033
	153.50	155.00	D039759	1.50	0.023		0.023
	155.00	156.50	D039760	1.50	0.026		0.026
	156.50	157.50	D039761	1.00	<0.005		0.001
	157.50	158.70	D039762	1.20	0.012		0.012
	158.70	160.00	D039764	1.30	0.046		0.046

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
169.80	175.20	SY; POR <b>Syérite; Porphyrique</b> Pink-green matrix with ~5% phenocrysts. Highly altered (sericite, chl) and sheared. Phenos are pale white to pink, subhedral, up to 1cm in length, fractured, locally hematite altered. Irregular qtz-carb veining.	160.00	161.50	D039765	1.50	0.010		0.010
			161.50	163.00	D039766	1.50	0.090		0.090
			163.00	164.00	D039767	1.00	0.181		0.181
			164.00	165.50	D039768	1.50	0.464		0.464
			165.50	167.00	D039769	1.50	0.050		0.050
			167.00	168.00	D039771	1.00	<0.005		0.001
			168.00	168.90	D039772	0.90	<0.005		0.001
			168.90	169.80	D039774	0.90	0.007		0.007
			169.80	171.50	D039775	1.70	0.015		0.015
			171.50	173.00	D039776	1.50	0.019		0.019
			173.00	174.00	D039777	1.00	0.198		0.198
			174.00	175.20	D039778	1.20	0.069		0.069
			175.20	176.50	D039779	1.30	<0.005		0.001
			176.50	178.20	D039780	1.70	0.009		0.009
			178.20	179.70	D039781	1.50	0.008		0.008
			179.70	180.80	D039782	1.10	0.016		0.016
			180.80	182.00	D039784	1.20	0.013		0.013
			182.00	183.20	D039785	1.20	0.006		0.006
			183.20	184.00	D039786	0.80	0.040		0.040
			184.00	185.00	D039787	1.00	0.019		0.019
185.00	186.50	D039788	1.50	0.045		0.045			
186.50	188.00	D039789	1.50	0.029		0.029			
188.00	189.50	D039790	1.50	0.005		0.005			
189.50	191.00	D039791	1.50	0.115		0.115			
191.00	192.50	D039792	1.50	0.006		0.006			
192.50	194.00	D039794	1.50	<0.005		0.001			
194.00	195.50	D039795	1.50	<0.005		0.001			
195.50	197.00	D039796	1.50	<0.005		0.001			
197.00	198.50	D039797	1.50	0.041		0.041			
198.50	200.00	D039798	1.50	0.051		0.051			
200.00	201.60	D039799	1.60	<0.005		0.001			
201.60	203.50	SY; POR <b>Syérite; Porphyrique</b> Pink-green matrix with ~5% phenocrysts. Phenos are	201.60	202.40	D039800	0.80	0.020		0.020
			202.40	203.50	D039801	1.10	0.185		0.185

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
grey-white to pink, eu to subhedral, up to 2.5cm in length, fractured, locally hematite altered. Contacts are clear but not sharp and defined by dark green (chl conc).			203.50	205.00	D039802	1.50	<0.005		0.001
			205.00	206.00	D039804	1.00	0.257		0.257
			206.00	207.40	D039805	1.40	0.053		0.053
			207.40	209.00	D039806	1.60	0.007		0.007
			209.00	209.90	D039807	0.90	0.005		0.005
			209.90	210.90	D039808	1.00	0.084		0.084
			210.90	212.00	D039809	1.10	0.184		0.184
			212.00	213.00	D039811	1.00	0.060		0.060
			213.00	214.00	D039812	1.00	0.235		0.235
			214.00	215.70	D039814	1.70	2.310		2.310
			215.70	217.40	D039815	1.70	1.100		1.100
			217.40	218.20	D039816	0.80	0.028		0.028
			218.20	219.50	D039817	1.30	0.020		0.020
			219.50	221.00	D039818	1.50	0.609		0.609
			221.00	222.20	D039819	1.20	0.125		0.125
		222.20	223.00	D039820	0.80	3.070		3.070	
222.30	222.70	SY; POR <b>Syénite; Porphyrique</b> Pink-green matrix with ~5% phenocrysts. Phenos are grey-white to pink, euhedral, up to 2.5cm in length, fractured, locally hematite altered. Contacts are clear but not sharp.							
223.00	227.00	HM <b>Hématisé</b> Weak carbonate alteration, strong pervasive hematite alteration, chl and sericite alteration.	223.00	224.00	D039821	1.00	1.620		1.620
			224.00	225.50	D039822	1.50	0.359		0.359
			225.50	227.00	D039824	1.50	0.527		0.527
227.00	258.50	CB <b>Carbonaté</b> Weak to strong, pervasive carbonate alteration.	227.00	228.50	D039825	1.50	0.087		0.087
			228.50	230.00	D039826	1.50	0.024		0.024
			230.00	231.50	D039827	1.50	0.010		0.010
			231.50	233.10	D039828	1.60	0.024		0.024
			233.10	233.90	D039829	0.80	0.215		0.215
			233.90	235.50	D039830	1.60	0.370		0.370
			235.50	236.50	D039831	1.00	0.120		0.120
			236.50	237.30	D039832	0.80	0.425		0.425
236.60	237.23	SY; POR <b>Syénite; Porphyrique</b>	237.30	239.00	D039834	1.70	0.400		0.400
			239.00	240.50	D039835	1.50	0.047		0.047

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
252.20	295.00	SY <b>Syénite 20°</b> Blue-grey to greenish, silica-carb flooded porphyritic syenite with abundant white-grey qtz carb veins. Unit interlayered with weakly foliated, ~20 deg TCA, chloritized syenite, pale green-yellow with localized pink colouring from hematite alteration. Unit is locally brecciated in areas of strong silica or chl-sericite flooding. Pervasive carbonate alteration, strong in areas of blue-grey discoloration. Trace up to 3% phenocrysts, highly altered (chl, sericite, hematite), sub to anhedral, generally around 5mm in size. Trace up to 2% py.	240.50	242.00	D039836	1.50	0.049		0.049
			242.00	243.50	D039837	1.50	0.121		0.121
			243.50	245.00	D039838	1.50	0.194		0.194
			245.00	246.50	D039839	1.50	0.107		0.107
			246.50	248.00	D039840	1.50	<0.005		0.001
			248.00	249.00	D039841	1.00	0.015		0.015
			249.00	250.50	D039842	1.50	0.009		0.009
			250.50	252.20	D039844	1.70	0.157		0.157
			252.20	253.00	D039845	0.80	1.575		1.575
			253.00	254.00	D039846	1.00	2.150		2.150
258.50	262.30	SI03 <b>Silicifié 3</b> Weak to moderate, pervasive silicification.	254.00	255.50	D039847	1.50	1.580		1.580
			255.50	257.00	D039848	1.50	3.010		3.010
			257.00	258.50	D039849	1.50	4.220		4.220
			258.50	260.00	D039851	1.50	4.110		4.110
262.30	267.50	CB <b>Carbonaté</b> Weak to strong carbonate alteration.	260.00	261.50	D039852	1.50	3.320		3.320
			261.50	262.30	D039854	0.80	5.420		5.420
			262.30	263.10	D039855	0.80	3.430		3.430
			263.10	264.50	D039856	1.40	2.230		2.230
267.50	269.00	SR <b>Séricitique</b> Moderate sericite alteration, chl alteration.	264.50	265.80	D039857	1.30	2.540		2.540
			265.80	267.50	D039858	1.70	1.485		1.485
			267.50	269.00	D039859	1.50	0.813		0.813
269.00	280.00	CB <b>Carbonaté</b> Weak to strong carbonate alteration.	269.00	270.00	D039860	1.00	0.252		0.252
			270.00	271.50	D039861	1.50	0.212		0.212
			271.50	272.30	D039862	0.80	0.102		0.102
			272.30	274.00	D039864	1.70	0.014		0.014
			274.00	275.00	D039865	1.00	0.037		0.037
			275.00	276.50	D039866	1.50	0.067		0.067
276.50	277.30	D039867	0.80	0.151		0.151			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
280.00	288.50	BR <b>bréchifié (matrice silice/carb)</b> Moderate degree of brecciation resulting from qtz-carb flooding.	277.30	278.20	D039868	0.90	0.296		0.296
			278.20	279.10	D039869	0.90	2.460		2.460
			279.10	280.00	D039870	0.90	2.610		2.610
			280.00	281.00	D039871	1.00	1.830		1.830
			281.00	282.50	D039872	1.50	1.755		1.755
			282.50	284.00	D039874	1.50	2.860		2.860
			284.00	285.50	D039875	1.50	1.755		1.755
			285.50	287.10	D039876	1.60	3.530		3.530
			287.10	288.50	D039877	1.40	1.435		1.435
288.50	293.00	CB <b>Carbonaté</b> Weak to strong carbonate alteration.	288.50	289.30	D039878	0.80	1.490		1.490
			289.30	290.20	D039879	0.90	1.560		1.560
			290.20	291.50	D039880	1.30	1.640		1.640
			291.50	293.00	D039881	1.50	0.854		0.854
293.00	295.00	SR <b>Séricitique</b> Strong bleaching and sericite alteration. Interlayered with carbonate altered blue-grey syenite.	293.00	294.00	D039882	1.00	0.234		0.234
			294.00	295.00	D039884	1.00	1.345		1.345
295.00	Fin du sondage Nombre d'échantillons : 216 Nombre d'échantillons QAQC : 31 Longueur totale échantillonnée : 292.70								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
8.50	10.00	D039643	D039642	1.50	0.157	0.157
17.00	17.00	D039650	M1	0.00	<0.005	0.001
20.00	20.00	D039653	J	0.00	0.777	0.777
33.50	35.00	D039663	D039662	1.50	0.013	0.013
47.00	47.00	D039673	K	0.00	1.060	1.060
60.50	62.00	D039683	D039682	1.50	0.005	0.005
69.50	69.50	D039690	M1	0.00	<0.005	0.001
72.50	72.50	D039693	L	0.00	2.160	2.160
86.00	87.50	D039703	D039702	1.50	<0.005	0.001
97.90	97.90	D039713	M	0.00	3.160	3.160
111.50	113.00	D039723	D039722	1.50	0.148	0.148
120.50	120.50	D039730	M1	0.00	0.005	0.005
123.00	123.00	D039733	J	0.00	0.763	0.763
134.80	136.00	D039743	D039742	1.20	0.045	0.045
145.40	145.40	D039753	K	0.00	0.994	0.994
157.50	158.70	D039763	D039762	1.20	0.010	0.010
165.50	165.50	D039770	M1	0.00	<0.005	0.001
168.00	168.00	D039773	L	0.00	2.100	2.100
179.70	180.80	D039783	D039782	1.10	0.018	0.018
191.00	191.00	D039793	M	0.00	3.130	3.130
203.50	205.00	D039803	D039802	1.50	<0.005	0.001
210.90	210.90	D039810	M1	0.00	<0.005	0.001
213.00	213.00	D039813	J	0.00	0.753	0.753
224.00	225.50	D039823	D039822	1.50	0.369	0.369
236.50	236.50	D039833	K	0.00	1.055	1.055
249.00	250.50	D039843	D039842	1.50	0.011	0.011
257.00	257.00	D039850	M1	0.00	0.020	0.020
260.00	260.00	D039853	L	0.00	2.150	2.150
271.50	272.30	D039863	D039862	0.80	0.118	0.118
281.00	281.00	D039873	M	0.00	3.160	3.160
293.00	294.00	D039883	D039882	1.00	0.218	0.218

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-217**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-05-13

Date de description :

Au :                      2010-05-18

Collet

UTM

Azimut :                      180.00°

Plongée :                      -62.00°

Longueur :                      461.00 m

Est                      631 100.1

Nord                      5 374 438.1

Élévation                      312.2

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	185.50°	-61.90°	Non
Reflex	8.00	185.00°	-62.00°	Non
Reflex	11.00	184.90°	-61.90°	Non
Reflex	14.00	185.30°	-61.90°	Non
Reflex	17.00	185.50°	-62.00°	Non
Reflex	20.00	185.60°	-62.00°	Non
Reflex	23.00	185.50°	-61.90°	Non
Reflex	26.00	185.60°	-61.70°	Non
Reflex	29.00	184.60°	-61.50°	Non
Reflex	32.00	182.30°	-61.40°	Non
Reflex	35.00	182.60°	-61.40°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	181.90°	-61.30°	Non
Reflex	41.00	182.20°	-61.30°	Non
Reflex	44.00	181.80°	-61.20°	Non
Reflex	47.00	182.40°	-61.10°	Non
Reflex	50.00	180.40°	-61.10°	Non
Reflex	53.00	183.90°	-61.00°	Non
Reflex	56.00	186.30°	-60.90°	Non
Reflex	59.00	187.90°	-60.80°	Non
Reflex	62.00	188.60°	-60.70°	Non
Reflex	65.00	187.40°	-60.70°	Non
Reflex	68.00	186.90°	-60.70°	Non
Reflex	71.00	186.50°	-60.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	186.40°	-60.60°	Non	Reflex	173.00	188.90°	-61.00°	Non
Reflex	77.00	186.00°	-60.60°	Non	Reflex	176.00	188.70°	-61.00°	Non
Reflex	80.00	186.20°	-60.70°	Non	Reflex	179.00	188.90°	-61.00°	Non
Reflex	83.00	186.20°	-60.70°	Non	Reflex	182.00	188.90°	-61.00°	Non
Reflex	86.00	185.70°	-60.70°	Non	Reflex	185.00	189.00°	-61.00°	Non
Reflex	89.00	186.00°	-60.70°	Non	Reflex	188.00	189.00°	-61.00°	Non
Reflex	92.00	186.30°	-60.70°	Non	Reflex	191.00	189.00°	-61.10°	Non
Reflex	95.00	186.40°	-60.70°	Non	Reflex	194.00	189.00°	-61.10°	Non
Reflex	98.00	186.60°	-60.80°	Non	Reflex	197.00	189.30°	-61.10°	Non
Reflex	101.00	186.60°	-60.70°	Non	Reflex	200.00	189.40°	-61.00°	Non
Reflex	104.00	187.00°	-60.70°	Non	Reflex	203.00	189.50°	-61.00°	Non
Reflex	107.00	186.80°	-60.80°	Non	Reflex	206.00	189.60°	-61.10°	Non
Reflex	110.00	187.00°	-60.80°	Non	Reflex	209.00	189.70°	-61.10°	Non
Reflex	113.00	187.30°	-60.80°	Non	Reflex	212.00	189.70°	-61.10°	Non
Reflex	116.00	187.40°	-60.80°	Non	Reflex	215.00	189.70°	-61.10°	Non
Reflex	119.00	187.40°	-60.80°	Non	Reflex	218.00	190.10°	-61.10°	Non
Reflex	122.00	187.50°	-60.80°	Non	Reflex	221.00	190.20°	-61.10°	Non
Reflex	125.00	187.70°	-60.80°	Non	Reflex	224.00	190.30°	-61.20°	Non
Reflex	128.00	187.80°	-60.90°	Non	Reflex	227.00	190.60°	-61.20°	Non
Reflex	131.00	187.70°	-60.90°	Non	Reflex	230.00	190.20°	-61.20°	Non
Reflex	134.00	187.90°	-60.90°	Non	Reflex	233.00	190.10°	-61.20°	Non
Reflex	137.00	187.80°	-60.90°	Non	Reflex	236.00	190.70°	-61.20°	Non
Reflex	140.00	188.00°	-61.00°	Non	Reflex	239.00	190.80°	-61.20°	Non
Reflex	143.00	188.20°	-61.00°	Non	Reflex	242.00	190.70°	-61.30°	Non
Reflex	146.00	188.10°	-61.00°	Non	Reflex	245.00	190.30°	-61.30°	Non
Reflex	149.00	188.10°	-61.00°	Non	Reflex	248.00	190.80°	-61.30°	Non
Reflex	152.00	188.10°	-61.00°	Non	Reflex	251.00	189.70°	-61.30°	Non
Reflex	155.00	188.20°	-61.00°	Non	Reflex	254.00	191.00°	-61.30°	Non
Reflex	158.00	188.40°	-61.00°	Non	Reflex	257.00	191.60°	-61.30°	Non
Reflex	161.00	188.40°	-61.00°	Non	Reflex	260.00	192.30°	-61.30°	Non
Reflex	164.00	188.40°	-61.00°	Non	Reflex	263.00	191.70°	-61.30°	Non
Reflex	167.00	188.30°	-61.00°	Non	Reflex	266.00	192.00°	-61.30°	Non
Reflex	170.00	188.60°	-61.00°	Non	Reflex	269.00	191.80°	-61.30°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	191.90°	-61.20°	Non	Reflex	371.00	194.60°	-61.40°	Non
Reflex	275.00	191.70°	-61.30°	Non	Reflex	374.00	194.90°	-61.40°	Non
Reflex	278.00	192.00°	-61.30°	Non	Reflex	377.00	194.90°	-61.40°	Non
Reflex	281.00	191.90°	-61.30°	Non	Reflex	380.00	194.90°	-61.30°	Non
Reflex	284.00	192.00°	-61.30°	Non	Reflex	383.00	196.60°	-61.30°	Non
Reflex	287.00	192.10°	-61.20°	Non	Reflex	386.00	195.50°	-61.20°	Non
Reflex	290.00	192.00°	-61.30°	Non	Reflex	389.00	195.90°	-61.00°	Non
Reflex	293.00	192.50°	-61.30°	Non	Reflex	392.00	195.40°	-60.90°	Non
Reflex	296.00	192.10°	-61.30°	Non	Reflex	395.00	195.40°	-60.80°	Non
Reflex	299.00	192.60°	-61.30°	Non	Reflex	398.00	195.60°	-60.60°	Non
Reflex	302.00	192.70°	-61.20°	Non	Reflex	401.00	195.70°	-60.50°	Non
Reflex	305.00	193.00°	-61.20°	Non	Reflex	404.00	195.30°	-60.30°	Non
Reflex	308.00	192.40°	-61.20°	Non	Reflex	407.00	195.70°	-60.20°	Non
Reflex	311.00	192.70°	-61.20°	Non	Reflex	410.00	195.80°	-59.90°	Non
Reflex	314.00	192.90°	-61.20°	Non	Reflex	413.00	195.90°	-59.70°	Non
Reflex	317.00	193.70°	-61.20°	Non	Reflex	416.00	196.00°	-59.50°	Non
Reflex	320.00	193.90°	-61.20°	Non	Reflex	419.00	196.10°	-59.40°	Non
Reflex	323.00	193.10°	-61.20°	Non	Reflex	422.00	196.00°	-59.40°	Non
Reflex	326.00	192.90°	-61.20°	Non	Reflex	425.00	196.30°	-59.30°	Non
Reflex	329.00	193.50°	-61.20°	Non	Reflex	428.00	196.30°	-59.30°	Non
Reflex	332.00	194.00°	-61.20°	Non	Reflex	431.00	196.50°	-59.30°	Non
Reflex	335.00	194.00°	-61.20°	Non	Reflex	434.00	196.50°	-59.30°	Non
Reflex	338.00	194.40°	-61.30°	Non	Reflex	437.00	196.60°	-59.20°	Non
Reflex	341.00	193.70°	-61.30°	Non	Reflex	440.00	196.80°	-59.20°	Non
Reflex	344.00	193.70°	-61.30°	Non	Reflex	443.00	196.80°	-59.20°	Non
Reflex	347.00	193.30°	-61.30°	Non	Reflex	446.00	197.10°	-59.20°	Non
Reflex	350.00	194.10°	-61.30°	Non	Reflex	449.00	197.20°	-59.20°	Non
Reflex	353.00	194.20°	-61.30°	Non	Reflex	452.00	197.30°	-59.10°	Non
Reflex	356.00	194.10°	-61.30°	Non	Reflex	455.00	197.50°	-59.10°	Non
Reflex	359.00	194.10°	-61.30°	Non	Reflex	458.00	197.50°	-59.00°	Non
Reflex	362.00	194.60°	-61.30°	Non	Reflex	461.00	197.70°	-59.00°	Non
Reflex	365.00	194.20°	-61.30°	Non					
Reflex	368.00	194.50°	-61.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.80	MT						
		<b>Mort-terrain</b>						
1.80	25.00	SY; FIN; POR	1.80	3.00	D018933	1.20	0.043	0.043
		<b>Syénite; Grains fins; Porphyrique</b>	3.00	4.50	D018934	1.50	0.006	0.006
		Syénite à grains fins avec passage porphyrique à porphyre Xmm.	4.50	6.00	D018935	1.50	0.026	0.026
			6.00	7.50	D018936	1.50	0.076	0.076
			7.50	9.00	D018938	1.50	0.010	0.010
			9.00	10.50	D018939	1.50	0.059	0.059
			10.50	12.00	D018940	1.50	0.597	0.597
			12.00	13.50	D018941	1.50	0.775	0.775
			13.50	15.00	D018942	1.50	0.090	0.090
			15.00	16.50	D018943	1.50	0.060	0.060
			16.50	18.00	D018944	1.50	1.040	1.040
			18.00	19.50	D018945	1.50	0.081	0.081
			19.50	21.00	D018946	1.50	<0.005	0.001
			21.00	22.50	D018948	1.50	0.005	0.005
			22.50	24.00	D018949	1.50	0.038	0.038
			24.00	25.00	D018950	1.00	<0.005	0.001
25.00	52.00	GA; FIN; MTY	25.00	26.50	D018951	1.50	<0.005	0.001
		<b>Gabbro; Grains fins; Grains moyens</b>	26.50	28.00	D018952	1.50	<0.005	0.001
		Gabbro, microgrenue, grains fins à grains moyens.	28.00	29.50	D018953	1.50	<0.005	0.001
			29.50	31.00	D018954	1.50	<0.005	0.001
			31.00	32.50	D018955	1.50	<0.005	0.001
			32.50	34.00	D018956	1.50	<0.005	0.001
			34.00	35.50	D018958	1.50	<0.005	0.001
			35.50	37.00	D018959	1.50	<0.005	0.001
			37.00	38.50	D018960	1.50	<0.005	0.001
			38.50	40.00	D018961	1.50	<0.005	0.001
			40.00	41.50	D018963	1.50	<0.005	0.001
			41.50	43.00	D018964	1.50	<0.005	0.001
			43.00	44.50	D018965	1.50	<0.005	0.001
			44.50	46.00	D018966	1.50	<0.005	0.001
			46.00	47.50	D018968	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
52.00	378.30	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains fins, porphyrique avec phénocristaux Xmm reparti inégalement.	47.50	49.00	D018969	1.50	<0.005		0.001
			49.00	50.50	D018970	1.50	<0.005		0.001
			50.50	52.00	D018971	1.50	<0.005		0.001
			52.00	53.50	D018972	1.50	<0.005		0.001
			53.50	55.00	D018973	1.50	<0.005		0.001
			55.00	56.50	D018974	1.50	<0.005		0.001
			56.50	58.00	D018975	1.50	<0.005		0.001
			58.00	59.50	D018976	1.50	<0.005		0.001
			59.50	61.00	D018978	1.50	<0.005		0.001
			61.00	62.50	D018979	1.50	0.015		0.015
			62.50	64.00	D018980	1.50	0.698		0.698
			64.00	65.50	D018981	1.50	0.077		0.077
			65.50	67.00	D018982	1.50	0.169		0.169
			67.00	68.50	D018983	1.50	0.007		0.007
			68.50	70.00	D018984	1.50	0.016		0.016
			70.00	71.50	D018985	1.50	0.184		0.184
			71.50	73.00	D018986	1.50	0.300		0.300
			73.00	74.50	D018988	1.50	0.257		0.257
			74.50	76.00	D018989	1.50	0.032		0.032
			76.00	77.50	D018990	1.50	0.029		0.029
			77.50	79.00	D018991	1.50	0.011		0.011
			79.00	80.50	D018992	1.50	0.012		0.012
			80.50	82.00	D018993	1.50	0.018		0.018
82.00	83.50	D018994	1.50	0.015		0.015			
83.50	85.00	D018995	1.50	0.628		0.628			
85.00	86.50	D018996	1.50	0.017		0.017			
86.50	88.00	D018998	1.50	0.006		0.006			
88.00	89.50	D018999	1.50	0.055		0.055			
89.50	91.00	D019000	1.50	0.045		0.045			
91.00	92.50	D019001	1.50	0.050		0.050			
92.50	94.00	D019003	1.50	0.034		0.034			
94.00	95.50	D019004	1.50	0.032		0.032			
95.50	97.00	D019005	1.50	0.344		0.344			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	97.00	98.50	D019006	1.50	0.371		0.371
	98.50	100.00	D019008	1.50	0.344		0.344
	100.00	101.50	D019009	1.50	0.385		0.385
	101.50	103.00	D019010	1.50	0.221		0.221
	103.00	104.50	D019011	1.50	0.149		0.149
	104.50	106.00	D019012	1.50	0.654		0.654
	106.00	107.50	D019013	1.50	0.026		0.026
	107.50	109.00	D019014	1.50	<0.005		0.001
	109.00	110.50	D019015	1.50	<0.005		0.001
	110.50	112.00	D019016	1.50	0.013		0.013
	112.00	113.50	D019018	1.50	0.019		0.019
	113.50	115.00	D019019	1.50	0.246		0.246
	115.00	116.50	D019020	1.50	0.321		0.321
	116.50	118.00	D019021	1.50	0.049		0.049
	118.00	119.50	D019022	1.50	0.085		0.085
	119.50	121.00	D019023	1.50	0.267		0.267
	121.00	122.50	D019024	1.50	0.164		0.164
	122.50	124.00	D019025	1.50	0.108		0.108
	124.00	125.50	D019026	1.50	0.038		0.038
	125.50	127.00	D019028	1.50	0.026		0.026
	127.00	128.50	D019029	1.50	0.090		0.090
	128.50	130.00	D019030	1.50	0.012		0.012
	130.00	131.50	D019031	1.50	0.009		0.009
	131.50	133.00	D019032	1.50	0.019		0.019
	133.00	134.50	D019033	1.50	0.026		0.026
	134.50	136.00	D019034	1.50	0.031		0.031
	136.00	137.50	D019035	1.50	0.012		0.012
	137.50	139.00	D019036	1.50	0.010		0.010
	139.00	140.50	D019038	1.50	0.044		0.044
	140.50	142.00	D019039	1.50	0.059		0.059
	142.00	143.50	D019040	1.50	0.034		0.034
	143.50	145.00	D019041	1.50	0.015		0.015
	145.00	146.50	D019043	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	146.50	148.00	D019044	1.50	0.019		0.019
	148.00	149.50	D019045	1.50	0.081		0.081
	149.50	151.00	D019046	1.50	0.524		0.524
	151.00	152.50	D019048	1.50	0.065		0.065
	152.50	154.00	D019049	1.50	0.019		0.019
	154.00	155.50	D019050	1.50	0.014		0.014
	155.50	157.00	D019051	1.50	0.012		0.012
	157.00	158.50	D019052	1.50	0.008		0.008
	158.50	160.00	D019053	1.50	0.006		0.006
	160.00	161.50	D019054	1.50	<0.005		0.001
	161.50	163.00	D019055	1.50	0.005		0.005
	163.00	164.50	D019056	1.50	0.014		0.014
	164.50	166.00	D019058	1.50	0.102		0.102
	166.00	167.50	D019059	1.50	7.220		7.220
	167.50	169.00	D019060	1.50	0.310		0.310
	169.00	170.50	D019061	1.50	0.076		0.076
	170.50	172.00	D019062	1.50	0.029		0.029
	172.00	173.50	D019063	1.50	0.145		0.145
	173.50	175.00	D019064	1.50	0.459		0.459
	175.00	176.50	D019065	1.50	0.317		0.317
	176.50	178.00	D019066	1.50	0.067		0.067
	178.00	179.50	D019068	1.50	0.181		0.181
	179.50	181.00	D019069	1.50	0.174		0.174
	181.00	182.50	D019070	1.50	0.084		0.084
	182.50	184.00	D019071	1.50	0.225		0.225
	184.00	185.50	D019072	1.50	1.040		1.040
	185.50	187.00	D019073	1.50	0.138		0.138
	187.00	188.50	D019074	1.50	0.024		0.024
	188.50	190.00	D019075	1.50	0.030		0.030
	190.00	191.50	D019076	1.50	0.104		0.104
	191.50	193.00	D019078	1.50	0.008		0.008
	193.00	194.50	D019079	1.50	0.087		0.087
	194.50	196.00	D019080	1.50	0.026		0.026



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	196.00	197.50	D019081	1.50	0.045		0.045
	197.50	199.00	D019083	1.50	0.150		0.150
	199.00	200.50	D019084	1.50	0.169		0.169
	200.50	202.00	D019085	1.50	0.060		0.060
	202.00	203.50	D019086	1.50	0.277		0.277
	203.50	205.00	D019088	1.50	0.188		0.188
	205.00	206.50	D019089	1.50	0.211		0.211
	206.50	208.00	D019090	1.50	0.030		0.030
	208.00	209.50	D019091	1.50	0.034		0.034
	209.50	211.00	D019092	1.50	0.006		0.006
	211.00	212.50	D019093	1.50	0.013		0.013
	212.50	214.00	D019094	1.50	<0.005		0.001
	214.00	215.50	D019095	1.50	0.011		0.011
	215.50	217.00	D019096	1.50	<0.005		0.001
	217.00	218.50	D019098	1.50	<0.005		0.001
	218.50	220.00	D019099	1.50	<0.005		0.001
	220.00	221.50	D019100	1.50	<0.005		0.001
	221.50	223.00	D019101	1.50	<0.005		0.001
	223.00	224.50	D019102	1.50	<0.005		0.001
	224.50	226.00	D019103	1.50	0.024		0.024
	226.00	227.50	D019104	1.50	0.005		0.005
	227.50	229.00	D019105	1.50	<0.005		0.001
	229.00	230.50	D019106	1.50	0.019		0.019
	230.50	232.00	D019108	1.50	<0.005		0.001
	232.00	233.50	D019109	1.50	0.034		0.034
	233.50	235.00	D019110	1.50	<0.005		0.001
	235.00	236.50	D019111	1.50	0.027		0.027
	236.50	238.00	D019112	1.50	0.026		0.026
	238.00	239.50	D019113	1.50	<0.005		0.001
	239.50	241.00	D019114	1.50	0.041		0.041
	241.00	242.50	D019115	1.50	0.018		0.018
	242.50	244.00	D019116	1.50	0.019		0.019
	244.00	245.50	D019118	1.50	0.047		0.047

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	245.50	247.00	D019119	1.50	0.080		0.080
	247.00	248.50	D019120	1.50	<0.005		0.001
	248.50	250.00	D019121	1.50	0.492		0.492
	250.00	251.50	D019123	1.50	0.009		0.009
	251.50	253.00	D019124	1.50	<0.005		0.001
	253.00	254.50	D019125	1.50	<0.005		0.001
	254.50	256.00	D019126	1.50	<0.005		0.001
	256.00	257.50	D019128	1.50	0.017		0.017
	257.50	259.00	D019129	1.50	<0.005		0.001
	259.00	260.50	D019130	1.50	<0.005		0.001
	260.50	262.00	D019131	1.50	0.039		0.039
	262.00	263.50	D019132	1.50	0.034		0.034
	263.50	265.00	D019133	1.50	0.006		0.006
	265.00	266.50	D019134	1.50	0.006		0.006
	266.50	268.00	D019135	1.50	0.008		0.008
	268.00	269.50	D019136	1.50	<0.005		0.001
	269.50	271.00	D019138	1.50	0.008		0.008
	271.00	272.50	D019139	1.50	<0.005		0.001
	272.50	274.00	D019140	1.50	0.013		0.013
	274.00	275.50	D019141	1.50	<0.005		0.001
	275.50	277.00	D019142	1.50	<0.005		0.001
	277.00	278.50	D019143	1.50	0.009		0.009
	278.50	280.00	D019144	1.50	0.011		0.011
	280.00	281.50	D019145	1.50	0.015		0.015
	281.50	283.00	D019146	1.50	1.140		1.140
	283.00	284.50	D019148	1.50	0.005		0.005
	284.50	286.00	D019149	1.50	0.020		0.020
	286.00	287.50	D019150	1.50	0.014		0.014
	287.50	289.00	D019151	1.50	<0.005		0.001
	289.00	290.50	D019152	1.50	0.005		0.005
	290.50	292.00	D019153	1.50	0.056		0.056
	292.00	293.50	D019154	1.50	0.005		0.005
	293.50	295.00	D019155	1.50	0.050		0.050

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	295.00	296.50	D019156	1.50	0.007		0.007
	296.50	298.00	D019158	1.50	0.006		0.006
	298.00	299.50	D019159	1.50	0.014		0.014
	299.50	301.00	D019160	1.50	0.164		0.164
	301.00	302.50	D019161	1.50	0.007		0.007
	302.50	304.00	D019163	1.50	0.008		0.008
	304.00	305.50	D019164	1.50	<0.005		0.001
	305.50	307.00	D019165	1.50	0.005		0.005
	307.00	308.50	D019166	1.50	0.006		0.006
	308.50	310.00	D019168	1.50	<0.005		0.001
	310.00	311.50	D019169	1.50	0.089		0.089
	311.50	313.00	D019170	1.50	0.275		0.275
	313.00	314.50	D019171	1.50	0.007		0.007
	314.50	316.00	D019172	1.50	0.006		0.006
	316.00	317.50	D019173	1.50	0.006		0.006
	317.50	319.00	D019174	1.50	0.005		0.005
	319.00	320.50	D019175	1.50	0.006		0.006
	320.50	322.00	D019176	1.50	0.005		0.005
	322.00	323.50	D019178	1.50	<0.005		0.001
	323.50	325.00	D019179	1.50	0.010		0.010
	325.00	326.50	D019180	1.50	<0.005		0.001
	326.50	328.00	D019181	1.50	0.006		0.006
	328.00	329.50	D019182	1.50	0.006		0.006
	329.50	331.00	D019183	1.50	0.005		0.005
	331.00	332.50	D019184	1.50	0.012		0.012
	332.50	334.00	D019185	1.50	0.005		0.005
	334.00	335.50	D019186	1.50	0.005		0.005
	335.50	337.00	D019188	1.50	0.006		0.006
	337.00	338.50	D019189	1.50	<0.005		0.001
	338.50	340.00	D019190	1.50	0.006		0.006
	340.00	341.50	D019191	1.50	<0.005		0.001
	341.50	343.00	D019192	1.50	<0.005		0.001
	343.00	344.50	D019193	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			344.50	346.00	D019194	1.50		0.020		0.020
			346.00	347.50	D019195	1.50		0.093		0.093
			347.50	349.00	D019196	1.50		0.060		0.060
			349.00	350.50	D019198	1.50		0.029		0.029
			350.50	352.00	D019199	1.50		0.038		0.038
			352.00	353.50	D019200	1.50		0.011		0.011
			353.50	355.00	D019201	1.50		0.086		0.086
			355.00	356.50	D019203	1.50		0.005		0.005
			356.50	358.00	D019204	1.50		0.015		0.015
			358.00	359.50	D019205	1.50		0.046		0.046
			359.50	361.00	D019206	1.50		0.132		0.132
			361.00	362.50	D019208	1.50		0.011		0.011
			362.50	364.00	D019209	1.50		<0.005		0.001
			364.00	365.50	D019210	1.50		<0.005		0.001
			365.50	367.00	D019211	1.50		0.006		0.006
			367.00	368.50	D019212	1.50		0.056		0.056
			368.50	370.00	D019213	1.50		0.292		0.292
			370.00	371.50	D019214	1.50		0.669		0.669
			371.50	373.00	D019215	1.50		0.005		0.005
			373.00	374.50	D019216	1.50		0.103		0.103
			374.50	376.00	D019218	1.50		<0.005		0.001
			376.00	377.50	D019219	1.50		<0.005		0.001
			377.50	378.30	D019220	0.80		<0.005		0.001
378.30	413.00	BA; MAS; AMY	378.30	379.50	D019221	1.20		<0.005		0.001
		<b>Basalte; Roche massive; Amygdalaire</b>	379.50	380.50	D019222	1.00		0.012		0.012
		Basalte massive avec passage amygdalaire, amygdules remplis de chlorite.	380.50	382.00	D019223	1.50		0.005		0.005
			382.00	383.50	D019224	1.50		0.024		0.024
			383.50	385.00	D019225	1.50		0.022		0.022
			385.00	386.50	D019226	1.50		<0.005		0.001
			386.50	388.00	D019228	1.50		<0.005		0.001
			388.00	389.50	D019229	1.50		<0.005		0.001
			389.50	391.00	D019230	1.50		<0.005		0.001
			391.00	392.50	D019231	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			392.50	394.00	D019232	1.50	<0.005		0.001
			394.00	395.50	D019233	1.50	<0.005		0.001
			395.50	397.00	D019234	1.50	<0.005		0.001
			397.00	398.50	D019235	1.50	<0.005		0.001
			398.50	400.00	D019236	1.50	<0.005		0.001
			400.00	401.50	D019238	1.50	<0.005		0.001
			401.50	403.00	D019239	1.50	<0.005		0.001
			403.00	404.50	D019240	1.50	<0.005		0.001
			404.50	406.00	D019241	1.50	<0.005		0.001
			406.00	407.50	D019243	1.50	<0.005		0.001
			407.50	409.00	D019244	1.50	<0.005		0.001
			409.00	410.00	D019245	1.00	<0.005		0.001
			410.00	411.50	D019246	1.50	<0.005		0.001
			411.50	413.00	D019248	1.50	<0.005		0.001
413.00	461.00	GA; FIN; MTY	413.00	414.50	D019249	1.50	<0.005		0.001
		<b>Gabbro; Grains fins; Grains moyens</b>	414.50	416.00	D019250	1.50	<0.005		0.001
		Gabbro, microgrenu, grains fins à moyens, avec phénocristaux Xmm.	416.00	417.50	D019251	1.50	<0.005		0.001
			417.50	419.00	D019252	1.50	<0.005		0.001
			419.00	420.50	D019253	1.50	<0.005		0.001
			420.50	422.00	D019254	1.50	<0.005		0.001
			422.00	423.50	D019255	1.50	<0.005		0.001
			423.50	425.00	D019256	1.50	<0.005		0.001
			425.00	426.50	D019258	1.50	<0.005		0.001
			426.50	428.00	D019259	1.50	<0.005		0.001
			428.00	429.50	D019260	1.50	<0.005		0.001
			429.50	431.00	D019261	1.50	<0.005		0.001
			431.00	432.50	D019262	1.50	<0.005		0.001
			432.50	434.00	D019263	1.50	<0.005		0.001
			434.00	435.50	D019264	1.50	<0.005		0.001
			435.50	437.00	D019265	1.50	<0.005		0.001
			437.00	438.50	D019266	1.50	<0.005		0.001
			438.50	440.00	D019268	1.50	<0.005		0.001
			440.00	441.50	D019269	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	441.50	443.00	D019270	1.50	<0.005		0.001
	443.00	444.50	D019271	1.50	<0.005		0.001
	444.50	446.00	D019272	1.50	<0.005		0.001
	446.00	447.50	D019273	1.50	<0.005		0.001
	447.50	449.00	D019274	1.50	<0.005		0.001
	449.00	450.50	D019275	1.50	<0.005		0.001
	450.50	452.00	D019276	1.50	<0.005		0.001
	452.00	453.50	D019278	1.50	<0.005		0.001
	453.50	455.00	D019279	1.50	0.014		0.014
	455.00	456.50	D019280	1.50	<0.005		0.001
	456.50	458.00	D019281	1.50	<0.005		0.001
	458.00	459.50	D019283	1.50	<0.005		0.001
	459.50	461.00	D019284	1.50	<0.005		0.001
461.00	Fin du sondage Nombre d'échantillons : 308 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 459.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	7.50	D018937	D018936	1.50	0.080	0.080
19.50	19.50	D018947	M	0.00	3.170	3.170
32.50	34.00	D018957	D018956	1.50	<0.005	0.001
38.50	38.50	D018962	M1	0.00	<0.005	0.001
44.50	44.50	D018967	J	0.00	0.644	0.644
58.00	59.50	D018977	D018976	1.50	<0.005	0.001
71.50	71.50	D018987	K	0.00	0.988	0.988
85.00	86.50	D018997	D018996	1.50	0.014	0.014
91.00	91.00	D019002	M1	0.00	0.049	0.049
97.00	97.00	D019007	L	0.00	2.020	2.020
110.50	112.00	D019017	D019016	1.50	0.014	0.014
124.00	124.00	D019027	M	0.00	2.840	2.840
137.50	139.00	D019037	D019036	1.50	0.005	0.005
143.50	143.50	D019042	M1	0.00	<0.005	0.001
149.50	149.50	D019047	J	0.00	0.785	0.785
163.00	164.50	D019057	D019056	1.50	0.019	0.019
176.50	176.50	D019067	K	0.00	1.140	1.140
190.00	191.50	D019077	D019076	1.50	0.106	0.106
196.00	196.00	D019082	M1	0.00	<0.005	0.001
202.00	202.00	D019087	L	0.00	2.330	2.330
215.50	217.00	D019097	D019096	1.50	<0.005	0.001
229.00	229.00	D019107	M	0.00	2.950	2.950
242.50	244.00	D019117	D019116	1.50	0.015	0.015
248.50	248.50	D019122	M1	0.00	<0.005	0.001
254.50	254.50	D019127	J	0.00	0.727	0.727
268.00	269.50	D019137	D019136	1.50	<0.005	0.001
281.50	281.50	D019147	K	0.00	0.042	0.042
295.00	296.50	D019157	D019156	1.50	0.006	0.006
301.00	301.00	D019162	M1	0.00	<0.005	0.001
307.00	307.00	D019167	L	0.00	1.860	1.860
320.50	322.00	D019177	D019176	1.50	0.009	0.009
334.00	334.00	D019187	M	0.00	2.870	2.870
347.50	349.00	D019197	D019196	1.50	0.125	0.125

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
353.50	353.50	D019202	M1	0.00	0.007	0.007
359.50	359.50	D019207	J	0.00	0.761	0.761
373.00	374.50	D019217	D019216	1.50	0.110	0.110
385.00	385.00	D019227	K	0.00	0.973	0.973
398.50	400.00	D019237	D019236	1.50	<0.005	0.001
404.50	404.50	D019242	M1	0.00	0.005	0.005
410.00	410.00	D019247	L	0.00	1.995	1.995
423.50	425.00	D019257	D019256	1.50	<0.005	0.001
437.00	437.00	D019267	M	0.00	3.000	3.000
450.50	452.00	D019277	D019276	1.50	<0.005	0.001
456.50	456.50	D019282	M1	0.00	<0.005	0.001



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-218**

Titre minier :

Section :                      630800

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy Gbaguidi

Lot :

Du :                      2010-05-09

Date de description :

Au :                      2010-05-14

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      470.00 m

Est	630 799.8
Nord	5 374 192.2
Élévation	300.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	360.00°	-57.50°	Non
Reflex	8.00	359.40°	-57.60°	Non
Reflex	11.00	4.20°	-57.50°	Oui
Reflex	14.00	359.80°	-57.50°	Non
Reflex	17.00	0.20°	-57.40°	Non
Reflex	20.00	0.40°	-57.50°	Non
Reflex	23.00	0.40°	-57.50°	Non
Reflex	26.00	0.70°	-57.70°	Non
Reflex	29.00	0.90°	-57.70°	Non
Reflex	32.00	0.90°	-57.80°	Non
Reflex	35.00	0.40°	-57.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.40°	-57.70°	Non
Reflex	41.00	1.10°	-57.70°	Non
Reflex	44.00	1.10°	-57.70°	Non
Reflex	47.00	1.60°	-57.60°	Non
Reflex	50.00	1.70°	-57.60°	Non
Reflex	53.00	1.80°	-57.60°	Non
Reflex	56.00	1.90°	-57.40°	Non
Reflex	59.00	1.90°	-57.30°	Non
Reflex	62.00	1.90°	-57.40°	Non
Reflex	65.00	2.00°	-57.50°	Non
Reflex	68.00	2.10°	-57.50°	Non
Reflex	71.00	2.20°	-57.40°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.10°	-57.40°	Non
Reflex	77.00	2.10°	-57.30°	Non
Reflex	80.00	1.70°	-57.30°	Non
Reflex	83.00	360.00°	-57.30°	Non
Reflex	86.00	3.90°	-57.30°	Oui
Reflex	89.00	2.40°	-57.30°	Oui
Reflex	92.00	352.80°	-57.20°	Oui
Reflex	95.00	0.20°	-57.20°	Non
Reflex	98.00	0.30°	-57.20°	Non
Reflex	101.00	1.00°	-57.20°	Non
Reflex	104.00	1.30°	-57.20°	Non
Reflex	107.00	1.50°	-57.20°	Non
Reflex	110.00	1.70°	-57.30°	Non
Reflex	113.00	1.30°	-57.30°	Non
Reflex	116.00	1.90°	-57.30°	Non
Reflex	119.00	1.70°	-57.30°	Non
Reflex	122.00	0.60°	-57.30°	Non
Reflex	125.00	1.10°	-57.30°	Non
Reflex	128.00	1.90°	-57.30°	Non
Reflex	131.00	1.40°	-57.30°	Non
Reflex	134.00	1.30°	-57.30°	Non
Reflex	137.00	2.40°	-57.30°	Non
Reflex	140.00	1.80°	-57.30°	Non
Reflex	143.00	1.90°	-57.30°	Non
Reflex	146.00	1.10°	-57.30°	Non
Reflex	149.00	2.00°	-57.30°	Non
Reflex	152.00	0.60°	-57.30°	Non
Reflex	155.00	359.10°	-57.30°	Non
Reflex	158.00	358.80°	-57.30°	Non
Reflex	161.00	0.90°	-57.40°	Non
Reflex	164.00	0.70°	-57.40°	Non
Reflex	167.00	0.90°	-57.40°	Non
Reflex	170.00	2.20°	-57.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	2.40°	-57.40°	Non
Reflex	176.00	1.60°	-57.40°	Non
Reflex	179.00	2.20°	-57.30°	Non
Reflex	182.00	2.50°	-57.30°	Non
Reflex	185.00	3.10°	-58.90°	Oui
Reflex	188.00	0.20°	-58.80°	Non
Reflex	191.00	358.10°	-58.50°	Non
Reflex	194.00	358.10°	-58.50°	Non
Reflex	197.00	358.80°	-58.40°	Non
Reflex	200.00	2.10°	-58.30°	Non
Reflex	203.00	1.10°	-58.40°	Non
Reflex	206.00	358.80°	-58.40°	Non
Reflex	209.00	359.20°	-58.40°	Non
Reflex	212.00	358.90°	-58.40°	Non
Reflex	215.00	358.80°	-58.40°	Non
Reflex	218.00	358.80°	-58.40°	Non
Reflex	221.00	359.00°	-58.40°	Non
Reflex	224.00	359.30°	-58.50°	Non
Reflex	227.00	359.40°	-58.50°	Non
Reflex	230.00	359.40°	-58.50°	Non
Reflex	233.00	0.30°	-58.50°	Non
Reflex	236.00	0.50°	-58.50°	Non
Reflex	239.00	0.10°	-58.60°	Non
Reflex	242.00	360.00°	-58.50°	Non
Reflex	245.00	0.30°	-58.60°	Non
Reflex	248.00	0.60°	-58.60°	Non
Reflex	251.00	0.50°	-58.60°	Non
Reflex	254.00	0.40°	-58.60°	Non
Reflex	257.00	0.60°	-58.50°	Non
Reflex	260.00	0.40°	-58.60°	Non
Reflex	263.00	0.50°	-58.50°	Non
Reflex	266.00	359.90°	-58.50°	Non
Reflex	269.00	359.60°	-58.60°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	359.00°	-58.60°	Non
Reflex	275.00	358.80°	-58.60°	Non
Reflex	278.00	358.60°	-58.60°	Non
Reflex	281.00	358.40°	-58.50°	Non
Reflex	284.00	358.40°	-58.40°	Non
Reflex	287.00	358.40°	-58.50°	Non
Reflex	290.00	358.30°	-58.50°	Non
Reflex	293.00	357.30°	-58.40°	Non
Reflex	296.00	0.10°	-58.40°	Non
Reflex	299.00	0.70°	-58.40°	Non
Reflex	302.00	0.10°	-58.40°	Non
Reflex	305.00	1.00°	-58.40°	Non
Reflex	308.00	0.80°	-58.40°	Non
Reflex	311.00	1.80°	-58.40°	Non
Reflex	314.00	359.80°	-58.40°	Non
Reflex	317.00	359.60°	-58.40°	Non
Reflex	320.00	359.40°	-58.30°	Non
Reflex	323.00	358.80°	-58.10°	Non
Reflex	326.00	358.80°	-58.10°	Non
Reflex	329.00	359.10°	-58.10°	Non
Reflex	332.00	359.60°	-58.10°	Non
Reflex	335.00	359.60°	-58.10°	Non
Reflex	338.00	0.80°	-58.00°	Non
Reflex	341.00	0.50°	-58.00°	Non
Reflex	344.00	0.50°	-58.00°	Non
Reflex	347.00	0.10°	-58.00°	Non
Reflex	350.00	0.60°	-57.20°	Non
Reflex	353.00	2.10°	-58.20°	Non
Reflex	356.00	3.40°	-58.10°	Oui
Reflex	359.00	4.30°	-58.10°	Oui
Reflex	362.00	1.50°	-58.10°	Non
Reflex	365.00	2.00°	-58.00°	Non
Reflex	368.00	0.40°	-58.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	4.60°	-58.00°	Oui
Reflex	374.00	1.60°	-58.00°	Non
Reflex	377.00	2.40°	-57.90°	Non
Reflex	380.00	3.10°	-57.90°	Non
Reflex	383.00	0.90°	-57.90°	Non
Reflex	386.00	1.80°	-57.90°	Non
Reflex	389.00	2.50°	-57.90°	Non
Reflex	392.00	359.90°	-57.90°	Oui
Reflex	395.00	359.40°	-58.00°	Oui
Reflex	398.00	2.50°	-57.90°	Non
Reflex	401.00	1.20°	-57.90°	Non
Reflex	404.00	2.50°	-57.90°	Non
Reflex	407.00	3.60°	-57.80°	Non
Reflex	410.00	2.10°	-57.80°	Non
Reflex	413.00	4.80°	-57.70°	Oui
Reflex	416.00	3.10°	-57.70°	Non
Reflex	419.00	3.70°	-57.60°	Non
Reflex	422.00	5.00°	-57.60°	Non
Reflex	425.00	4.70°	-57.60°	Non
Reflex	428.00	4.80°	-57.60°	Non
Reflex	431.00	4.90°	-57.60°	Non
Reflex	434.00	4.90°	-57.60°	Non
Reflex	437.00	4.30°	-57.50°	Non
Reflex	440.00	5.30°	-57.60°	Non
Reflex	443.00	4.80°	-57.50°	Non
Reflex	446.00	4.50°	-57.50°	Non
Reflex	449.00	5.00°	-57.50°	Non
Reflex	452.00	3.50°	-57.40°	Oui
Reflex	455.00	4.60°	-57.50°	Non
Reflex	458.00	5.00°	-57.50°	Non
Reflex	461.00	4.80°	-57.40°	Non
Reflex	464.00	4.90°	-57.50°	Non
Reflex	467.00	5.00°	-57.50°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	4.80°	-57.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.00	MT						
		<b>Mort-terrain</b>						
2.00	46.50	SY; POR	2.00	3.50	D023091	1.50	0.529	0.529
		<b>Syénite; Porphyrique</b>	3.50	5.00	D023092	1.50	0.333	0.333
		Syénite porphyrique hématisée et séricitisée, localement sub-bréchique.	5.00	6.50	D023093	1.50	0.368	0.368
			6.50	8.00	D023094	1.50	0.109	0.109
			8.00	9.50	D023096	1.50	0.220	0.220
			9.50	11.00	D023097	1.50	0.027	0.027
			11.00	12.50	D023098	1.50	<0.005	0.001
			12.50	14.00	D023099	1.50	<0.005	0.001
			14.00	15.50	D023100	1.50	<0.005	0.001
			15.50	17.00	D023101	1.50	0.008	0.008
			17.00	18.50	D023102	1.50	0.078	0.078
			18.50	20.00	D023103	1.50	0.011	0.011
			20.00	21.50	D023104	1.50	0.012	0.012
			21.50	23.00	D023106	1.50	0.037	0.037
			23.00	24.50	D023107	1.50	0.135	0.135
			24.50	26.00	D023108	1.50	0.158	0.158
			26.00	27.50	D023109	1.50	0.063	0.063
			27.50	29.00	D023110	1.50	0.075	0.075
			29.00	30.50	D023111	1.50	0.050	0.050
			30.50	32.00	D023112	1.50	0.093	0.093
			32.00	33.50	D023113	1.50	0.026	0.026
			33.50	35.00	D023114	1.50	0.183	0.183
			35.00	36.50	D023116	1.50	0.187	0.187
			36.50	38.00	D023117	1.50	0.298	0.298
			38.00	39.50	D023118	1.50	0.108	0.108
			39.50	41.00	D023119	1.50	0.094	0.094
			41.00	42.50	D023121	1.50	0.086	0.086
			42.50	44.00	D023122	1.50	0.312	0.312
			44.00	45.00	D023123	1.00	0.414	0.414
			45.00	46.50	D023124	1.50	0.552	0.552
46.50	105.00	BA; AMY	46.50	48.00	D023126	1.50	0.768	0.768
		<b>Basalte 30°; Amygdalaire</b>						

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Basalte amygdalaire, localement silicifié et bréchifié, hématisé et séricitisé.	48.00	49.50	D023127	1.50	2.010		2.010
	49.50	51.00	D023128	1.50	0.010		0.010
	51.00	52.50	D023129	1.50	0.648		0.648
	52.50	54.00	D023130	1.50	0.349		0.349
	54.00	55.50	D023131	1.50	0.043		0.043
	55.50	57.00	D023132	1.50	0.287		0.287
	57.00	58.50	D023133	1.50	0.018		0.018
	58.50	60.00	D023134	1.50	0.019		0.019
	60.00	61.50	D023136	1.50	0.132		0.132
	61.50	63.00	D023137	1.50	0.359		0.359
	63.00	64.50	D023138	1.50	0.038		0.038
	64.50	66.00	D023139	1.50	0.029		0.029
	66.00	67.50	D023140	1.50	0.049		0.049
	67.50	69.00	D023141	1.50	0.329		0.329
	69.00	70.50	D023142	1.50	4.540		4.540
	70.50	71.90	D023143	1.40	5.660		5.660
	71.90	72.90	D023144	1.00	2.110		2.110
	72.90	74.50	D023146	1.60	0.434		0.434
	74.50	76.00	D023147	1.50	0.470		0.470
	76.00	77.00	D023148	1.00	0.038		0.038
	77.00	78.00	D023149	1.00	1.835		1.835
	78.00	79.50	D023150	1.50	0.022		0.022
	79.50	81.00	D023151	1.50	0.007		0.007
	81.00	82.50	D023152	1.50	0.031		0.031
	82.50	84.00	D023153	1.50	1.470		1.470
	84.00	85.50	D023154	1.50	0.117		0.117
	85.50	87.00	D023156	1.50	0.013		0.013
	87.00	88.50	D023157	1.50	0.781		0.781
	88.50	90.00	D023158	1.50	0.755		0.755
	90.00	91.50	D023159	1.50	0.099		0.099
91.50	93.00	D023161	1.50	0.026		0.026	
93.00	94.50	D023162	1.50	0.005		0.005	
94.50	96.00	D023163	1.50	<0.005		0.001	

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
105.00	117.40	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique séricitisée et hématisée.	96.00	97.50	D023164	1.50	<0.005		0.001
			97.50	99.00	D023166	1.50	0.007		0.007
			99.00	100.50	D023167	1.50	0.006		0.006
			100.50	102.00	D023168	1.50	0.051		0.051
			102.00	103.30	D023169	1.30	0.005		0.005
			103.30	105.00	D023170	1.70	0.006		0.006
			105.00	106.50	D023171	1.50	0.022		0.022
			106.50	108.00	D023172	1.50	<0.005		0.001
			108.00	109.50	D023173	1.50	<0.005		0.001
			109.50	111.00	D023174	1.50	<0.005		0.001
			111.00	112.50	D023176	1.50	0.005		0.005
			112.50	114.00	D023177	1.50	<0.005		0.001
			114.00	115.70	D023178	1.70	0.005		0.005
			115.70	117.40	D023179	1.70	0.012		0.012
117.40	119.00	D023180	1.60	0.015		0.015			
119.00	129.40	SY; POR <b>Syénite 40°; Porphyrique</b> Syénite porphyrique séricitisée, chloritisée et hématisée.	119.00	120.10	D023181	1.10	0.005		0.005
			120.10	121.80	D023182	1.70	0.144		0.144
			121.80	123.50	D023183	1.70	0.070		0.070
			123.50	125.00	D023184	1.50	0.389		0.389
			125.00	126.50	D023186	1.50	0.090		0.090
			126.50	128.00	D023187	1.50	1.420		1.420
			128.00	129.40	D023188	1.40	0.781		0.781
129.40	131.00	GA <b>Gabbro 45°</b> Gabbro massive à leucocène.	129.40	131.00	D023189	1.60	0.013		0.013
			131.00	132.70	D023190	1.70	0.007		0.007
132.70	186.80	GA <b>Gabbro 30°</b> Gabbro massive à leucocène.	132.70	134.40	D023191	1.70	<0.005		0.001
			134.40	136.00	D023192	1.60	0.005		0.005
			136.00	137.50	D023193	1.50	<0.005		0.001
			137.50	139.00	D023194	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	139.00	140.50	D023196	1.50	<0.005		0.001
	140.50	142.00	D023197	1.50	<0.005		0.001
	142.00	143.50	D023198	1.50	0.006		0.006
	143.50	145.00	D023199	1.50	<0.005		0.001
	145.00	146.50	D023201	1.50	<0.005		0.001
	146.50	148.00	D023202	1.50	<0.005		0.001
	148.00	149.50	D023203	1.50	<0.005		0.001
	149.50	151.00	D023204	1.50	<0.005		0.001
	151.00	152.50	D023206	1.50	<0.005		0.001
	152.50	154.00	D023207	1.50	<0.005		0.001
	154.00	155.50	D023208	1.50	<0.005		0.001
	155.50	157.00	D023209	1.50	<0.005		0.001
	157.00	158.50	D023210	1.50	<0.005		0.001
	158.50	160.00	D023211	1.50	<0.005		0.001
	160.00	161.50	D023212	1.50	<0.005		0.001
	161.50	163.00	D023213	1.50	<0.005		0.001
	163.00	164.50	D023214	1.50	<0.005		0.001
	164.50	166.00	D023216	1.50	0.005		0.005
	166.00	167.50	D023217	1.50	0.007		0.007
	167.50	169.00	D023218	1.50	<0.005		0.001
	169.00	170.50	D023219	1.50	<0.005		0.001
	170.50	172.00	D023220	1.50	0.005		0.005
	172.00	173.50	D023221	1.50	0.026		0.026
	173.50	175.00	D023222	1.50	0.013		0.013
	175.00	176.50	D023223	1.50	<0.005		0.001
	176.50	178.00	D023224	1.50	<0.005		0.001
	178.00	179.50	D023226	1.50	<0.005		0.001
	179.50	181.00	D023227	1.50	<0.005		0.001
	181.00	182.50	D023228	1.50	<0.005		0.001
	182.50	184.00	D023229	1.50	<0.005		0.001
	184.00	185.50	D023230	1.50	<0.005		0.001
	185.50	186.80	D023231	1.30	<0.005		0.001
186.80	190.00	NR					
Carotte perdue							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
190.00	210.60	Carotte perdue, cime de sable. BA; AMY <b>Basalte 30°; Amygdalaire</b> Basalte amygdalaire massive, localement remplacé, bréchifiée et hématisé.	190.00	191.00	D023232	1.00	0.008		0.008
			191.00	192.00	D023233	1.00	3.240		3.240
			192.00	193.50	D023234	1.50	0.008		0.008
			193.50	195.00	D023236	1.50	0.020		0.020
			195.00	196.50	D023237	1.50	0.006		0.006
			196.50	198.00	D023238	1.50	0.351		0.351
			198.00	199.50	D023239	1.50	<0.005		0.001
			199.50	201.00	D023241	1.50	0.007		0.007
			201.00	202.60	D023242	1.60	0.029		0.029
			202.60	204.30	D023243	1.70	0.012		0.012
			204.30	206.00	D023244	1.70	2.900		2.900
			206.00	207.50	D023246	1.50	1.035		1.035
			207.50	209.00	D023247	1.50	3.270		3.270
			209.00	210.60	D023248	1.60	1.150		1.150
210.60	470.00	SY; POR <b>Syénite 45°; Porphyrique</b> Syénite porphyrique, hématisé, localement silicifiée, bréchifiée et remplacée.	210.60	212.00	D023249	1.40	0.114		0.114
			212.00	213.60	D023250	1.60	0.077		0.077
			213.60	215.00	D023251	1.40	1.205		1.205
			215.00	216.50	D023252	1.50	3.000		3.000
			216.50	218.00	D023253	1.50	2.090		2.090
			218.00	219.60	D023254	1.60	2.830		2.830
			219.60	221.30	D023256	1.70	1.705		1.705
			221.30	223.00	D023257	1.70	1.210		1.210
			223.00	224.50	D023258	1.50	0.684		0.684
			224.50	226.10	D023259	1.60	0.538		0.538
			226.10	227.50	D023260	1.40	0.746		0.746
			227.50	228.70	D023261	1.20	0.733		0.733
			228.70	230.00	D023262	1.30	1.360		1.360
			230.00	231.50	D023263	1.50	0.272		0.272
			231.50	233.00	D023264	1.50	0.116		0.116
			233.00	234.50	D023266	1.50	0.274		0.274
			234.50	236.00	D023267	1.50	0.068		0.068
			236.00	237.50	D023268	1.50	0.372		0.372

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	237.50	239.00	D023269	1.50	0.020		0.020
	239.00	240.50	D023270	1.50	0.419		0.419
	240.50	242.00	D023271	1.50	0.406		0.406
	242.00	243.50	D023272	1.50	0.045		0.045
	243.50	245.00	D023273	1.50	<0.005		0.001
	245.00	246.50	D023274	1.50	<0.005		0.001
	246.50	248.00	D023276	1.50	<0.005		0.001
	248.00	249.50	D023277	1.50	0.010		0.010
	249.50	251.00	D023278	1.50	0.005		0.005
	251.00	252.50	D023279	1.50	<0.005		0.001
	252.50	254.00	D023281	1.50	0.009		0.009
	254.00	255.50	D023282	1.50	<0.005		0.001
	255.50	257.00	D023283	1.50	<0.005		0.001
	257.00	258.50	D023284	1.50	0.148		0.148
	258.50	260.00	D023286	1.50	<0.005		0.001
	260.00	261.50	D023287	1.50	<0.005		0.001
	261.50	263.00	D023288	1.50	0.881		0.881
	263.00	264.50	D023289	1.50	0.568		0.568
	264.50	266.00	D023290	1.50	<0.005		0.001
	266.00	267.50	D023291	1.50	<0.005		0.001
	267.50	269.00	D023292	1.50	<0.005		0.001
	269.00	270.50	D023293	1.50	<0.005		0.001
	270.50	272.00	D023294	1.50	<0.005		0.001
	272.00	273.50	D023296	1.50	0.090		0.090
	273.50	275.00	D023297	1.50	0.018		0.018
	275.00	276.50	D023298	1.50	<0.005		0.001
	276.50	278.00	D023299	1.50	<0.005		0.001
	278.00	279.50	D023300	1.50	<0.005		0.001
	279.50	281.00	D023301	1.50	0.186		0.186
	281.00	282.50	D023302	1.50	<0.005		0.001
	282.50	284.00	D023303	1.50	0.015		0.015
	284.00	285.50	D023304	1.50	0.009		0.009
	285.50	287.00	D023306	1.50	0.021		0.021

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	287.00	288.50	D023307	1.50	0.012		0.012
	288.50	290.00	D023308	1.50	0.013		0.013
	290.00	291.50	D023309	1.50	1.495		1.495
	291.50	293.00	D023310	1.50	0.031		0.031
	293.00	294.50	D023311	1.50	0.007		0.007
	294.50	296.00	D023312	1.50	<0.005		0.001
	296.00	297.50	D023313	1.50	0.175		0.175
	297.50	299.00	D023314	1.50	0.119		0.119
	299.00	300.50	D023316	1.50	0.145		0.145
	300.50	302.00	D023317	1.50	0.092		0.092
	302.00	303.50	D023318	1.50	0.017		0.017
	303.50	305.00	D023319	1.50	<0.005		0.001
	305.00	306.50	D023321	1.50	0.050		0.050
	306.50	308.00	D023322	1.50	0.007		0.007
	308.00	309.50	D023323	1.50	0.016		0.016
	309.50	311.00	D023324	1.50	0.030		0.030
	311.00	312.50	D023326	1.50	0.012		0.012
	312.50	314.00	D023327	1.50	0.008		0.008
	314.00	315.50	D023328	1.50	0.065		0.065
	315.50	317.00	D023329	1.50	0.028		0.028
	317.00	318.50	D023330	1.50	0.010		0.010
	318.50	320.00	D023331	1.50	0.013		0.013
	320.00	321.50	D023332	1.50	0.016		0.016
	321.50	323.00	D023333	1.50	0.006		0.006
	323.00	324.50	D023334	1.50	<0.005		0.001
	324.50	326.00	D023336	1.50	0.011		0.011
	326.00	327.50	D023337	1.50	0.071		0.071
	327.50	329.00	D023338	1.50	0.012		0.012
	329.00	330.50	D023339	1.50	<0.005		0.001
	330.50	332.00	D023340	1.50	0.009		0.009
	332.00	333.50	D023341	1.50	0.008		0.008
	333.50	335.00	D023342	1.50	0.040		0.040
	335.00	336.50	D023343	1.50	0.030		0.030

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	336.50	338.00	D023344	1.50	0.019		0.019
	338.00	339.50	D023346	1.50	0.005		0.005
	339.50	341.00	D023347	1.50	0.010		0.010
	341.00	342.50	D023348	1.50	<0.005		0.001
	342.50	344.00	D023349	1.50	0.005		0.005
	344.00	345.50	D023350	1.50	<0.005		0.001
	345.50	347.00	D023351	1.50	<0.005		0.001
	347.00	348.50	D023352	1.50	0.017		0.017
	348.50	350.00	D023353	1.50	<0.005		0.001
	350.00	351.50	D023354	1.50	0.007		0.007
	351.50	353.00	D023356	1.50	0.010		0.010
	353.00	354.50	D023357	1.50	0.019		0.019
	354.50	356.00	D023358	1.50	<0.005		0.001
	356.00	357.50	D023359	1.50	0.005		0.005
	357.50	359.00	D023361	1.50	0.005		0.005
	359.00	360.50	D023362	1.50	0.005		0.005
	360.50	362.00	D023363	1.50	0.008		0.008
	362.00	363.00	D023364	1.00	0.135		0.135
	363.00	364.00	D023366	1.00	1.340		1.340
	364.00	365.00	D023367	1.00	0.429		0.429
	365.00	366.50	D023368	1.50	0.064		0.064
	366.50	368.00	D023369	1.50	0.115		0.115
	368.00	369.50	D023370	1.50	0.028		0.028
	369.50	371.00	D023371	1.50	0.016		0.016
	371.00	372.50	D023372	1.50	0.007		0.007
	372.50	374.00	D023373	1.50	0.044		0.044
	374.00	375.50	D023374	1.50	0.911		0.911
	375.50	377.00	D023376	1.50	0.270		0.270
	377.00	378.50	D023377	1.50	0.005		0.005
	378.50	380.00	D023378	1.50	<0.005		0.001
	380.00	381.50	D023379	1.50	<0.005		0.001
	381.50	383.00	D023380	1.50	0.048		0.048
	383.00	384.50	D023381	1.50	0.142		0.142

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	384.50	386.00	D023382	1.50	0.045		0.045
	386.00	387.50	D023383	1.50	<0.005		0.001
	387.50	389.00	D023384	1.50	0.005		0.005
	389.00	390.50	D023386	1.50	0.032		0.032
	390.50	392.00	D023387	1.50	0.033		0.033
	392.00	393.50	D023388	1.50	0.039		0.039
	393.50	395.00	D023389	1.50	0.099		0.099
	395.00	396.50	D023390	1.50	0.024		0.024
	396.50	398.00	D023391	1.50	0.359		0.359
	398.00	399.50	D023392	1.50	0.007		0.007
	399.50	401.00	D023393	1.50	<0.005		0.001
	401.00	402.50	D023394	1.50	0.032		0.032
	402.50	404.00	D023396	1.50	0.208		0.208
	404.00	405.50	D023397	1.50	0.440		0.440
	405.50	407.00	D023398	1.50	0.132		0.132
	407.00	408.50	D023399	1.50	0.336		0.336
	408.50	410.00	D023400	1.50	0.052		0.052
	410.00	411.30	D023401	1.30	0.146		0.146
	411.30	413.00	D023402	1.70	0.011		0.011
	413.00	414.50	D023403	1.50	<0.005		0.001
	414.50	416.00	D023404	1.50	<0.005		0.001
	416.00	417.50	D023406	1.50	<0.005		0.001
	417.50	419.00	D023407	1.50	0.035		0.035
	419.00	420.50	D023408	1.50	0.569		0.569
	420.50	422.00	D023409	1.50	0.025		0.025
	422.00	423.50	D023410	1.50	<0.005		0.001
	423.50	425.00	D023411	1.50	0.011		0.011
	425.00	426.50	D023412	1.50	<0.005		0.001
	426.50	428.00	D023413	1.50	<0.005		0.001
	428.00	429.50	D023414	1.50	<0.005		0.001
	429.50	431.00	D023416	1.50	<0.005		0.001
	431.00	432.50	D023417	1.50	<0.005		0.001
	432.50	434.00	D023418	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	434.00	435.00	D023419	1.00	0.005		0.005
	435.00	436.00	D023420	1.00	0.027		0.027
	436.00	437.50	D023421	1.50	0.404		0.404
	437.50	439.10	D023422	1.60	0.811		0.811
	439.10	440.50	D023423	1.40	0.015		0.015
	440.50	442.00	D023424	1.50	0.005		0.005
	442.00	443.50	D023426	1.50	<0.005		0.001
	443.50	445.00	D023427	1.50	0.038		0.038
	445.00	446.50	D023428	1.50	0.040		0.040
	446.50	448.00	D023429	1.50	0.007		0.007
	448.00	449.50	D023430	1.50	0.078		0.078
	449.50	451.20	D023431	1.70	1.000		1.000
	451.20	452.90	D023432	1.70	<0.005		0.001
	452.90	454.50	D023433	1.60	0.022		0.022
	454.50	456.00	D023434	1.50	0.012		0.012
	456.00	457.50	D023436	1.50	0.009		0.009
	457.50	459.00	D023437	1.50	0.016		0.016
	459.00	460.50	D023438	1.50	0.090		0.090
	460.50	462.00	D023439	1.50	0.018		0.018
	462.00	463.50	D023441	1.50	0.024		0.024
	463.50	465.00	D023442	1.50	0.081		0.081
	465.00	466.50	D023443	1.50	0.012		0.012
	466.50	468.00	D023444	1.50	0.251		0.251
	468.00	469.00	D023446	1.00	0.040		0.040
	469.00	470.00	D023447	1.00	0.018		0.018
470.00	Fin du sondage Nombre d'échantillons : 313 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 464.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.50	6.50	D023095	L	0.00	2.130	2.130
20.00	21.50	D023105	D023104	1.50	0.006	0.006
33.50	33.50	D023115	M	0.00	3.390	3.390
39.50	39.50	D023120	M1	0.00	<0.005	0.001
45.00	46.50	D023125	D023124	1.50	0.473	0.473
58.50	58.50	D023135	J	0.00	0.729	0.729
71.90	72.90	D023145	D023144	1.00	1.320	1.320
84.00	84.00	D023155	L	0.00	2.020	2.020
90.00	90.00	D023160	M1	0.00	<0.005	0.001
96.00	97.50	D023165	D023164	1.50	<0.005	0.001
109.50	109.50	D023175	J	0.00	0.780	0.780
123.50	125.00	D023185	D023184	1.50	0.216	0.216
137.50	137.50	D023195	K	0.00	1.075	1.075
143.50	143.50	D023200	M1	0.00	<0.005	0.001
149.50	151.00	D023205	D023204	1.50	<0.005	0.001
163.00	163.00	D023215	L	0.00	2.300	2.300
176.50	178.00	D023225	D023224	1.50	<0.005	0.001
192.00	192.00	D023235	M	0.00	3.170	3.170
198.00	198.00	D023240	M1	0.00	<0.005	0.001
204.30	206.00	D023245	D023244	1.70	2.910	2.910
218.00	218.00	D023255	J	0.00	0.841	0.841
231.50	233.00	D023265	D023264	1.50	0.116	0.116
245.00	245.00	D023275	M	0.00	3.170	3.170
251.00	251.00	D023280	M1	0.00	<0.005	0.001
257.00	258.50	D023285	D023284	1.50	0.184	0.184
270.50	270.50	D023295	J	0.00	0.719	0.719
284.00	285.50	D023305	D023304	1.50	0.009	0.009
297.50	297.50	D023315	J	0.00	0.802	0.802
303.50	303.50	D023320	M1	0.00	<0.005	0.001
309.50	311.00	D023325	D023324	1.50	0.037	0.037
323.00	323.00	D023335	L	0.00	2.370	2.370
336.50	338.00	D023345	D023344	1.50	0.016	0.016
350.00	350.00	D023355	M	0.00	3.190	3.190

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
356.00	356.00	D023360	M1	0.00	<0.005	0.001
362.00	363.00	D023365	D023364	1.00	0.160	0.160
374.00	374.00	D023375	J	0.00	0.836	0.836
387.50	389.00	D023385	D023384	1.50	<0.005	0.001
401.00	401.00	D023395	K	0.00	1.070	1.070
414.50	416.00	D023405	D023404	1.50	0.006	0.006
428.00	428.00	D023415	J	0.00	0.776	0.776
440.50	442.00	D023425	D023424	1.50	<0.005	0.001
454.50	454.50	D023435	K	0.00	0.968	0.968
460.50	460.50	D023440	M1	0.00	<0.005	0.001
466.50	468.00	D023445	D023444	1.50	0.236	0.236



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-219**

Titre minier :

Section :                      630800

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Myriam St-Louis

Lot :

Du :                      2010-05-14

Date de description :

Au :                      2010-05-18

Collet

UTM

Azimut :                      0.00°

Plongée :                      -67.00°

Longueur :                      437.00 m

Est                              630 800.0

Nord                              5 374 190.0

Élévation                      300.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	359.30°	-66.70°	Non
Reflex	8.00	358.90°	-66.50°	Non
Reflex	11.00	359.40°	-66.50°	Non
Reflex	14.00	357.90°	-66.50°	Non
Reflex	17.00	359.00°	-66.50°	Non
Reflex	20.00	358.80°	-66.50°	Non
Reflex	23.00	358.70°	-66.60°	Non
Reflex	26.00	359.10°	-66.60°	Non
Reflex	29.00	359.70°	-66.70°	Non
Reflex	32.00	358.10°	-66.70°	Non
Reflex	35.00	359.30°	-66.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.50°	-66.90°	Non
Reflex	41.00	359.60°	-66.90°	Non
Reflex	44.00	359.80°	-66.90°	Non
Reflex	47.00	359.90°	-66.80°	Non
Reflex	50.00	0.20°	-67.10°	Non
Reflex	53.00	0.40°	-66.90°	Non
Reflex	56.00	0.10°	-66.90°	Non
Reflex	59.00	359.60°	-66.90°	Non
Reflex	62.00	0.80°	-66.90°	Non
Reflex	65.00	1.20°	-66.80°	Non
Reflex	68.00	359.60°	-66.80°	Non
Reflex	71.00	360.00°	-66.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.80°	-66.90°	Non
Reflex	77.00	0.70°	-66.80°	Non
Reflex	80.00	1.00°	-66.80°	Non
Reflex	83.00	1.40°	-66.80°	Non
Reflex	86.00	1.20°	-66.90°	Non
Reflex	89.00	1.60°	-66.80°	Non
Reflex	92.00	1.50°	-66.80°	Non
Reflex	95.00	1.50°	-66.80°	Non
Reflex	98.00	1.60°	-66.70°	Non
Reflex	101.00	2.00°	-66.70°	Non
Reflex	104.00	357.10°	-66.80°	Non
Reflex	107.00	2.80°	-66.80°	Non
Reflex	110.00	3.30°	-66.80°	Non
Reflex	113.00	3.40°	-66.80°	Non
Reflex	116.00	5.20°	-66.70°	Non
Reflex	119.00	5.40°	-66.80°	Non
Reflex	122.00	2.20°	-66.80°	Non
Reflex	125.00	2.70°	-66.80°	Non
Reflex	128.00	2.80°	-66.80°	Non
Reflex	131.00	2.60°	-66.80°	Non
Reflex	134.00	3.10°	-66.80°	Oui
Reflex	137.00	2.30°	-66.80°	Non
Reflex	140.00	2.50°	-66.70°	Non
Reflex	143.00	2.40°	-66.70°	Non
Reflex	146.00	2.70°	-66.70°	Non
Reflex	149.00	3.00°	-66.70°	Non
Reflex	152.00	3.20°	-66.80°	Non
Reflex	155.00	3.40°	-66.80°	Non
Reflex	158.00	3.90°	-66.70°	Non
Reflex	161.00	3.70°	-66.80°	Non
Reflex	164.00	4.30°	-66.80°	Non
Reflex	167.00	2.70°	-66.80°	Non
Reflex	170.00	4.40°	-66.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	3.60°	-66.80°	Non
Reflex	176.00	3.50°	-66.80°	Non
Reflex	179.00	3.60°	-66.90°	Non
Reflex	182.00	4.50°	-66.80°	Oui
Reflex	185.00	3.90°	-66.80°	Non
Reflex	188.00	3.90°	-66.80°	Non
Reflex	191.00	3.50°	-66.90°	Non
Reflex	194.00	3.40°	-66.70°	Non
Reflex	197.00	2.70°	-66.80°	Non
Reflex	200.00	4.50°	-66.80°	Oui
Reflex	203.00	3.30°	-66.80°	Non
Reflex	206.00	4.10°	-66.80°	Non
Reflex	209.00	4.10°	-66.80°	Non
Reflex	212.00	3.30°	-66.80°	Non
Reflex	215.00	3.00°	-66.80°	Non
Reflex	218.00	3.20°	-66.80°	Non
Reflex	221.00	3.00°	-66.80°	Non
Reflex	224.00	3.20°	-66.80°	Non
Reflex	227.00	2.70°	-66.80°	Non
Reflex	230.00	2.50°	-66.80°	Non
Reflex	233.00	3.50°	-66.80°	Non
Reflex	236.00	2.00°	-66.70°	Non
Reflex	239.00	2.00°	-66.70°	Non
Reflex	242.00	3.80°	-66.60°	Non
Reflex	245.00	4.20°	-66.40°	Non
Reflex	248.00	4.40°	-66.30°	Non
Reflex	251.00	1.30°	-66.10°	Oui
Reflex	254.00	2.90°	-66.10°	Non
Reflex	257.00	3.00°	-66.10°	Non
Reflex	260.00	3.70°	-66.20°	Non
Reflex	263.00	3.80°	-66.10°	Non
Reflex	266.00	3.90°	-66.10°	Non
Reflex	269.00	4.00°	-66.20°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	4.20°	-66.20°	Non	Reflex	371.00	3.20°	-65.50°	Non
Reflex	275.00	3.80°	-66.20°	Non	Reflex	374.00	3.10°	-65.50°	Non
Reflex	278.00	3.50°	-66.10°	Non	Reflex	377.00	3.10°	-65.50°	Non
Reflex	281.00	3.40°	-66.10°	Non	Reflex	380.00	3.10°	-65.50°	Non
Reflex	284.00	3.10°	-66.10°	Non	Reflex	383.00	3.20°	-65.50°	Non
Reflex	287.00	3.20°	-66.10°	Non	Reflex	386.00	3.50°	-65.50°	Non
Reflex	290.00	3.90°	-66.00°	Non	Reflex	389.00	4.60°	-65.50°	Non
Reflex	293.00	3.50°	-66.00°	Non	Reflex	392.00	3.90°	-65.50°	Non
Reflex	296.00	3.70°	-66.00°	Non	Reflex	395.00	3.70°	-65.50°	Non
Reflex	299.00	3.70°	-66.10°	Non	Reflex	398.00	3.30°	-65.60°	Non
Reflex	302.00	3.60°	-66.10°	Non	Reflex	401.00	4.20°	-65.60°	Non
Reflex	305.00	4.00°	-66.00°	Non	Reflex	404.00	3.50°	-65.70°	Non
Reflex	308.00	3.80°	-66.00°	Non	Reflex	407.00	1.20°	-65.70°	Non
Reflex	311.00	3.70°	-65.90°	Non	Reflex	410.00	1.90°	-65.70°	Non
Reflex	314.00	3.70°	-65.80°	Non	Reflex	413.00	6.50°	-65.70°	Oui
Reflex	317.00	3.60°	-65.70°	Non	Reflex	416.00	3.10°	-65.80°	Non
Reflex	320.00	3.60°	-65.70°	Non	Reflex	419.00	3.00°	-65.70°	Non
Reflex	323.00	3.50°	-65.70°	Non	Reflex	422.00	1.20°	-65.80°	Non
Reflex	326.00	3.70°	-65.70°	Non	Reflex	425.00	1.00°	-65.80°	Non
Reflex	329.00	3.80°	-65.70°	Non	Reflex	428.00	0.60°	-65.90°	Non
Reflex	332.00	3.90°	-65.60°	Non	Reflex	431.00	1.00°	-65.80°	Non
Reflex	335.00	3.60°	-65.60°	Non	Reflex	434.00	1.30°	-65.90°	Non
Reflex	338.00	3.60°	-65.60°	Non	Reflex	437.00	1.40°	-65.90°	Non
Reflex	341.00	3.10°	-65.60°	Non					
Reflex	344.00	3.50°	-65.60°	Non					
Reflex	347.00	3.40°	-65.60°	Non					
Reflex	350.00	3.40°	-65.50°	Non					
Reflex	353.00	3.30°	-65.60°	Non					
Reflex	356.00	3.30°	-65.50°	Non					
Reflex	359.00	3.30°	-65.50°	Non					
Reflex	362.00	3.20°	-65.50°	Non					
Reflex	365.00	3.20°	-65.50°	Non					
Reflex	368.00	3.20°	-65.50°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.20	MT <b>Mort-terrain</b>						
2.20	40.40	SY <b>Syénite</b> Syenite rouge à rouge violacé avec larges (quelques mm à plus d'un cm) phénocristaux de feldspath isométriques généralement partiellement ou complètement remplacé par de la chlorite (zonation), parfois remplacé par de l'hématite ou de la séricite, quelques petites zones sont magnétisées, pyrite très fine et disséminée. Complètement hématisée, quelques endroits chloritisés (et beaucoup de cheveux chloritisés), quelques zones sont légèrement silicifiées. Présence de séricite sous forme de grains ainsi que dans plusieurs cheveux, veinules et veines, quelques veines et veinules de quartz gris, quelques cheveux et veinules carbonatés.						
2.20	40.40	HM <b>Hématisé</b> Syénite fortement hématisée rouge à rouge violacé, chloritisée à quelques endroits, silicifiée à d'autres.	2.20	3.60	D038077	1.40	0.179	0.179
			3.60	5.00	D038078	1.40	0.103	0.103
			5.00	6.50	D038079	1.50	0.297	0.297
			6.50	8.00	D038081	1.50	0.290	0.290
			8.00	9.50	D038082	1.50	0.025	0.025
			9.50	11.00	D038083	1.50	0.176	0.176
			11.00	12.50	D038084	1.50	0.059	0.059
			12.50	14.00	D038085	1.50	0.059	0.059
			14.00	15.50	D038086	1.50	0.029	0.029
			15.50	17.00	D038087	1.50	0.005	0.005
			17.00	18.50	D038088	1.50	0.045	0.045
			18.50	20.00	D038089	1.50	0.016	0.016
			20.00	21.50	D038090	1.50	0.009	0.009
			21.50	23.00	D038091	1.50	0.010	0.010
			23.00	24.50	D038092	1.50	0.008	0.008
			24.50	26.00	D038094	1.50	0.012	0.012
			26.00	27.50	D038095	1.50	0.042	0.042
			27.50	29.00	D038096	1.50	0.008	0.008
			29.00	30.50	D038097	1.50	0.092	0.092

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
40.40	50.70	<p>SY</p> <p><b>Syénite</b></p> <p>Syénite fortement silicifiée, quelques endroits séricitisés, chloritisés ou hématisés. Généralement gris foncé avec des passages plus beiges, verdâtres ou rosés. Quelques restants d'anciens phénocristaux à quelques endroits (petits, altérés et avec les bords généralement arrondi et diffus). Très fine pyrite disséminée.</p>	30.50	32.00	D038098	1.50	0.089		0.089
			32.00	33.50	D038099	1.50	0.062		0.062
			33.50	35.00	D038100	1.50	0.070		0.070
			35.00	36.50	D038101	1.50	0.031		0.031
			36.50	38.00	D038102	1.50	0.017		0.017
			38.00	39.20	D038104	1.20	0.303		0.303
			39.20	40.40	D038105	1.20	0.097		0.097
40.40	50.70	<p>SI; SR; CH; HM</p> <p><b>Silicifié; Séricitique; Chloriteux; Hématisé</b></p> <p>Syénite fortement silicifiée et par endroits séricitisée, chloritisée et/ou hématisée. Fin légèrement moins silicifiée et plus séricitisée et chloritisée.</p>	40.40	41.50	D038106	1.10	0.975		0.975
			41.50	43.00	D038107	1.50	1.355		1.355
			43.00	44.50	D038108	1.50	1.210		1.210
			44.50	46.00	D038109	1.50	0.182		0.182
			46.00	47.50	D038111	1.50	0.259		0.259
			47.50	48.60	D038112	1.10	0.075		0.075
			48.60	49.80	D038114	1.20	0.390		0.390
50.70	71.50	<p>SY</p> <p><b>Syénite</b></p> <p>Syenite rouge à rouge violacé avec phénocristaux de feldspath de quelques mm à 1 cm, parfois partiellement zonés et plusieurs avec les bords arrondis, plusieurs zones sont magnétisées, pyrite très fine et disséminée. Complètement hématisée, quelques endroits silicifiés, d'autres chloritisés (et beaucoup de cheveux chloritisés). Présence de séricite sous forme de grains ainsi que dans plusieurs cheveux, veinules et veines, quelques veines et veinules de quartz gris.</p>	49.80	50.70	D038115	0.90	0.008		0.008
			50.70	52.00	D038116	1.30	0.007		0.007
			52.00	53.50	D038117	1.50	0.022		0.022
			53.50	55.00	D038118	1.50	0.006		0.006
			55.00	56.50	D038119	1.50	0.012		0.012
			56.50	58.00	D038120	1.50	0.086		0.086
			58.00						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
71.50	108.00	BA <b>Basalte</b> Basalte altéré, généralement fortement silicifié, séricitizé, hématisé et/ou chloritizé à plusieurs endroits. Plusieurs amygdules (yeux de quartz), quelques endroits bréchifiés. Très fine pyrite disséminée en plusieurs endroits. Plusieurs cheveux, veinules et veines avec quartz, feldspath, plusieurs chloritisés.	58.00	59.50	D038121	1.50	0.169		0.169
			59.50	61.00	D038122	1.50	0.017		0.017
			61.00	62.50	D038124	1.50	0.030		0.030
			62.50	64.00	D038125	1.50	0.195		0.195
			64.00	65.50	D038126	1.50	0.007		0.007
			65.50	67.00	D038127	1.50	0.122		0.122
			67.00	68.50	D038128	1.50	0.490		0.490
			68.50	70.00	D038129	1.50	0.019		0.019
			70.00	71.50	D038130	1.50	0.084		0.084
			71.50	108.00	SI; SR; HM; CH <b>Silicifié; Séricitique; Hématisé; Chloriteux</b> Altération variable, généralement silicifié mais aussi séricitizé, chloritizé et/ou hématisé en plusieurs endroits, certaines parties sont moins silicifiées que d'autres et plus chloritisées.	71.50	73.00	D038131	1.50
73.00	74.50	D038132				1.50	0.969		0.969
74.50	76.00	D038134				1.50	2.530		2.530
76.00	77.50	D038135				1.50	0.787		0.787
77.50	79.00	D038136				1.50	0.670		0.670
79.00	80.50	D038137				1.50	1.340		1.340
80.50	82.00	D038138				1.50	0.310		0.310
82.00	83.50	D038139				1.50	0.026		0.026
83.50	85.00	D038140				1.50	0.020		0.020
85.00	86.50	D038141				1.50	0.103		0.103
86.50	88.00	D038142				1.50	0.248		0.248
88.00	89.50	D038144				1.50	0.648		0.648
89.50	91.10	D038145				1.60	0.614		0.614
91.10	92.20	D038146				1.10	0.771		0.771
92.20	93.30	D038147				1.10	0.104		0.104
93.30	94.50	D038148				1.20	0.023		0.023
94.50	95.60	D038149				1.10	0.051		0.051
95.60	96.60	D038151				1.00	0.394		0.394
96.60	97.50	D038152	0.90	0.659		0.659			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
108.00	191.20	<p>SY</p> <p><b>Syénite</b></p> <p>Syénite rouge foncé fortement hématisée avec quelques passages chloritisés et d'autres silicifiés, plusieurs phénocristaux de feldspath zonés (remplacés partiellement ou parfois complètement par de l'hématite, de la chlorite ou de la séricite), quelques uns isométriques mais la plupart avec les bords arrondis, magnétique à plusieurs endroits, pyrite très fine disséminée. Présence de séricite surtout sous forme de grains mais aussi dans plusieurs cheveux, veinules et veines, quelques veines et veinules de quartz gris, spécularite dans plusieurs veinules, plusieurs cheveux chloritisés.</p>	97.50	99.00	D038154	1.50	0.128		0.128
			99.00	100.50	D038155	1.50	0.040		0.040
			100.50	102.00	D038156	1.50	0.187		0.187
			102.00	103.30	D038157	1.30	1.600		1.600
			103.30	104.50	D038158	1.20	0.252		0.252
			104.50	106.00	D038159	1.50	1.015		1.015
			106.00	107.00	D038160	1.00	3.050		3.050
			107.00	108.00	D038161	1.00	5.830		5.830
			108.00	109.50	D038162	1.50	1.985		1.985
			109.50	111.00	D038164	1.50	2.300		2.300
			111.00	112.50	D038165	1.50	0.952		0.952
			112.50	114.00	D038166	1.50	0.015		0.015
			114.00	115.50	D038167	1.50	0.059		0.059
			115.50	117.00	D038168	1.50	0.027		0.027
			117.00	118.50	D038169	1.50	0.083		0.083
			118.50	120.00	D038170	1.50	0.065		0.065
			120.00	121.50	D038171	1.50	0.044		0.044
			121.50	123.00	D038172	1.50	0.016		0.016
			123.00	124.50	D038174	1.50	0.065		0.065
			124.50	126.00	D038175	1.50	0.022		0.022
126.00	127.50	D038176	1.50	0.018		0.018			
127.50	129.00	D038177	1.50	0.226		0.226			
129.00	130.50	D038178	1.50	0.311		0.311			
130.50	132.00	D038179	1.50	0.039		0.039			
132.00	133.60	D038180	1.60	0.048		0.048			
108.00	133.60	<p>HM; CH</p> <p><b>Hématisé; Chloriteux</b></p> <p>Syénite hématisée avec plusieurs passages chloritisés et quelques uns silicifiés. Plus chloritisée vers la fin.</p>							
133.40	133.60	<p>FAI</p> <p><b>Faille 20°</b></p> <p>Faille avec boue de faille sur 7 cm d'épaisseur ainsi que plusieurs fragments.</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
133.60	138.70	HM; SI; SR <b>Hématisé; Silicifié; Séricitique</b> Zone très hématisée mais également avec un léger apport de silice (plusieurs veines de quartz blanc, quelques unes de quartz plus gris), plusieurs zones séricitisées, feldspath (dans plusieurs veines ainsi que quelques phenocristaux).	133.60	135.00	D038181	1.40	0.167		0.167
			135.00	136.50	D038182	1.50	0.016		0.016
			136.50	137.60	D038184	1.10	0.488		0.488
			137.60	138.70	D038185	1.10	0.367		0.367
138.70	139.90	HM; CH <b>Hématisé; Chloriteux</b> Syénite hématisée avec plusieurs passages chloritisés et quelques veines de quartz gris.	138.70	139.90	D038186	1.20	2.060		2.060
139.90	142.40	GA <b>Gabbro 35°</b> Intrusion mafique gris verdâtre, légèrement chloritisée et quelques endroits séricitisés, ankérite, grains de leucoxène, feldspath, légèrement schisteux (orientation 30 degrés), fragmenté.	139.90	141.10	D038187	1.20	0.052		0.052
			141.10	142.40	D038188	1.30	0.027		0.027
141.80	142.25	FRC <b>Fracturé 30°</b> Zone fracturée contenant une faille avec boue de faille sur 3 cm d'épaisseur (située à 142m).							
142.20	191.20	HM; CH <b>Hématisé; Chloriteux</b> Syénite hématisée avec plusieurs passages chloritisés. Plusieurs phénocristaux complètement remplacés par de la chlorite.	142.40	144.00	D038189	1.60	0.005		0.005
			144.00	145.50	D038191	1.50	<0.005		0.001
			145.50	147.00	D038192	1.50	<0.005		0.001
			147.00	148.50	D038194	1.50	<0.005		0.001
			148.50	150.00	D038195	1.50	<0.005		0.001
			150.00	151.50	D038196	1.50	<0.005		0.001
			151.50	153.00	D038197	1.50	0.034		0.034
			153.00	154.50	D038198	1.50	<0.005		0.001
			154.50	156.00	D038199	1.50	0.010		0.010
			156.00	157.50	D038200	1.50	0.007		0.007
			157.50	159.00	D038201	1.50	0.039		0.039
			159.00	160.50	D038202	1.50	0.015		0.015
			160.50	162.00	D038204	1.50	<0.005		0.001
162.00	163.10	D038205	1.10	<0.005		0.001			
163.10	164.00	D038206	0.90	<0.005		0.001			
164.00	165.00	D038207	1.00	<0.005		0.001			
165.00	166.50	D038208	1.50	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
191.20	250.00	BA; AMY <b>Basalte 10*; Amygdalaire</b> Basalte altéré avec beaucoup d'amygdules (parfois remplacées et zonées), quelques possibles bordures de coussins, roche assez grenue dans certaines régions, quelques endroit bréchifiés, très fine pyrite disséminée en plusieurs endroits. Plusieurs cheveux et veinules de chlorite, plusieurs autres de séricite.	166.50	168.00	D038209	1.50	<0.005		0.001
			168.00	169.50	D038210	1.50	<0.005		0.001
			169.50	171.00	D038211	1.50	<0.005		0.001
			171.00	172.50	D038212	1.50	<0.005		0.001
			172.50	174.00	D038214	1.50	<0.005		0.001
			174.00	175.50	D038215	1.50	<0.005		0.001
			175.50	177.00	D038216	1.50	<0.005		0.001
			177.00	178.50	D038217	1.50	<0.005		0.001
			178.50	180.00	D038218	1.50	<0.005		0.001
			180.00	181.50	D038219	1.50	<0.005		0.001
			181.50	183.00	D038220	1.50	<0.005		0.001
			183.00	184.50	D038221	1.50	<0.005		0.001
			184.50	186.00	D038222	1.50	<0.005		0.001
			186.00	187.50	D038224	1.50	<0.005		0.001
			187.50	189.00	D038225	1.50	<0.005		0.001
			189.00	190.10	D038226	1.10	<0.005		0.001
			190.10	191.20	D038227	1.10	0.008		0.008
			191.20	192.50	D038228	1.30	0.052		0.052
			192.50	194.00	D038229	1.50	0.006		0.006
			194.00	195.50	D038231	1.50	<0.005		0.001
			195.50	197.00	D038232	1.50	<0.005		0.001
			197.00	198.40	D038234	1.40	0.005		0.005
			198.40	200.00	D038235	1.60	1.350		1.350
			200.00	201.50	D038236	1.50	0.336		0.336
			201.50	203.00	D038237	1.50	0.105		0.105
			203.00	204.50	D038238	1.50	0.037		0.037
			204.50	206.00	D038239	1.50	0.777		0.777
206.00	207.50	D038240	1.50	0.022		0.022			
207.50	209.00	D038241	1.50	0.023		0.023			
209.00	210.50	D038242	1.50	1.390		1.390			
210.50	212.00	D038244	1.50	0.544		0.544			
212.00	213.50	D038245	1.50	0.896		0.896			
213.50	215.00	D038246	1.50	0.237		0.237			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
191.20	216.50	SI; CH; SR; HM <b>Silicifié; Chloriteux; Séricitique; Hématisé</b> Basalte généralement assez silicifié avec des passages chloritisés, et/ou hématisés et/ou séricitisés (altération et couleur très variables).	215.00	216.50	D038247	1.50	0.809		0.809
216.50	231.60	SR; CH; HM <b>Séricitique; Chloriteux; Hématisé</b> Altération surtout en séricite, mais aussi généralement en chlorite et plusieurs passages hématisés. Vert très pale avec passages violacés et d'autres moins séricitisés et d'une couleur vert foncé. Plusieurs zones magnétiques semblent associées avec ces zones plus foncées. Plusieurs yeux de quartz, roche assez grenue à plusieurs endroits.	216.50	218.00	D038248	1.50	0.006		0.006
			218.00	219.50	D038249	1.50	0.014		0.014
			219.50	221.00	D038250	1.50	<0.005		0.001
			221.00	222.50	D038251	1.50	0.051		0.051
			222.50	224.00	D038252	1.50	<0.005		0.001
			224.00	225.50	D038254	1.50	0.013		0.013
			225.50	227.00	D038255	1.50	0.878		0.878
			227.00	228.50	D038256	1.50	0.005		0.005
			228.50	230.00	D038257	1.50	<0.005		0.001
			230.00	231.60	D038258	1.60	<0.005		0.001
231.60	250.00	CB; SR; CH <b>Carbonaté; Séricitique; Chloriteux</b> Roches légèrement carbonatées, séricitisées et chloritisées par endroits.	231.60	233.00	D038259	1.40	<0.005		0.001
			233.00	234.50	D038260	1.50	<0.005		0.001
			234.50	236.00	D038261	1.50	<0.005		0.001
			236.00	237.50	D038262	1.50	<0.005		0.001
			237.50	239.00	D038264	1.50	<0.005		0.001
			239.00	240.50	D038265	1.50	<0.005		0.001
			240.50	242.00	D038266	1.50	<0.005		0.001
			242.00	243.50	D038267	1.50	<0.005		0.001
			243.50	245.00	D038268	1.50	<0.005		0.001
			245.00	246.50	D038269	1.50	<0.005		0.001
246.28	246.34	FAI <b>Faïlle 40°</b> Faïlle avec boue de faïlle et fragments.	246.50	248.00	D038271	1.50	0.010		0.010
			248.00	249.00	D038272	1.00	1.175		1.175
			249.00	250.00	D038274	1.00	0.029		0.029
250.00	369.50	SY <b>Syénite</b> Syénite rouge violacé, fortement hématisée et faiblement carbonatée et/ou chloritisée par endroits, plusieurs phénocristaux de feldspath zonés (remplacés partiellement ou parfois complètement par de l'hématite, de la chlorite ou de la séricite), quelques uns isométriques	250.00	251.50	D038275	1.50	0.034		0.034
			251.50	253.00	D038276	1.50	<0.005		0.001
			253.00	254.50	D038277	1.50	0.010		0.010
			254.50	256.00	D038278	1.50	0.036		0.036

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
250.00	256.00	HM; CH <b>Hématisé; Chloriteux</b> Syénite hématisée et généralement faiblement chloritisée.						
256.00	288.20	HM; CB; CH <b>Hématisé; Carbonaté; Chloriteux</b> Syénite hématisée et faiblement carbonaté (augmente légèrement avec la profondeur) et chloritisée.	256.00	257.50	D038279	1.50	<0.005	0.001
			257.50	259.00	D038280	1.50	<0.005	0.001
			259.00	260.50	D038281	1.50	0.013	0.013
			260.50	262.00	D038282	1.50	<0.005	0.001
			262.00	263.50	D038284	1.50	<0.005	0.001
			263.50	265.00	D038285	1.50	0.135	0.135
			265.00	266.50	D038286	1.50	<0.005	0.001
			266.50	268.00	D038287	1.50	<0.005	0.001
			268.00	269.50	D038288	1.50	0.131	0.131
			269.50	271.00	D038289	1.50	0.156	0.156
			271.00	272.50	D038290	1.50	0.035	0.035
			272.50	273.50	D038291	1.00	0.029	0.029
			273.50	275.00	D038292	1.50	0.005	0.005
			275.00	276.50	D038294	1.50	0.016	0.016
			276.50	278.00	D038295	1.50	0.013	0.013
			278.00	279.50	D038296	1.50	<0.005	0.001
			279.50	281.00	D038297	1.50	0.010	0.010
			281.00	282.50	D038298	1.50	0.229	0.229
			282.50	284.00	D038299	1.50	0.091	0.091
			284.00	285.50	D038300	1.50	0.094	0.094
			285.50	287.00	D038301	1.50	0.078	0.078
			287.00	288.20	D038302	1.20	<0.005	0.001
288.20	295.00	SI; CB <b>Silicifié; Carbonaté</b> Syénite fortement silicifiée et modérément carbonatée, phénocristaux complètement remplacés par de la silice et de la séricite ayant des bords diffus, faiblement hématisée en quelques endroits, riche en fine pyrite disséminée.	288.20	289.50	D038304	1.30	2.820	2.820
			289.50	291.00	D038305	1.50	1.880	1.880
			291.00	292.50	D038306	1.50	3.210	3.210
			292.50	294.00	D038307	1.50	6.840	6.840
			294.00	295.00	D038308	1.00	2.400	2.400

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
295.00	321.10	HM; SI; CB; CH <b>Hématisé; Silicifié; Carbonaté; Chloriteux</b> Syénite fortement hématisée et silicifié dans plusieurs zones, généralement légèrement carbonatée (surtout au début) et chloritisée. Séricite en grains et dans plusieurs cheveux également.	295.00	296.50	D038309	1.50	0.201		0.201
			296.50	298.00	D038311	1.50	0.177		0.177
			298.00	299.50	D038312	1.50	0.276		0.276
			299.50	301.00	D038314	1.50	0.604		0.604
			301.00	302.50	D038315	1.50	0.134		0.134
			302.50	304.00	D038316	1.50	0.203		0.203
			304.00	305.50	D038317	1.50	0.606		0.606
			305.50	307.00	D038318	1.50	0.673		0.673
			307.00	308.50	D038319	1.50	0.180		0.180
			308.50	310.00	D038320	1.50	0.596		0.596
			310.00	311.50	D038321	1.50	0.382		0.382
			311.50	313.00	D038322	1.50	0.573		0.573
			313.00	314.50	D038324	1.50	0.114		0.114
			314.50	316.00	D038325	1.50	0.395		0.395
			316.00	317.50	D038326	1.50	1.175		1.175
			317.50	319.00	D038327	1.50	1.315		1.315
			319.00	320.00	D038328	1.00	1.200		1.200
			320.00	321.10	D038329	1.10	1.765		1.765
			321.10	369.50	HM; CH; CB; SR; SI <b>Hématisé; Chloriteux; Carbonaté; Séricitique; Silicifié</b> Syénite fortement hématisée, légèrement chloritisée et carbonatée, plusieurs zones décimétriques séricitisées et quelques unes centimétriques légèrement silicifiées.	321.10	322.50	D038330	1.40
322.50	324.00	D038331				1.50	0.015		0.015
324.00	325.50	D038332				1.50	0.041		0.041
325.50	327.00	D038334				1.50	<0.005		0.001
327.00	328.50	D038335				1.50	<0.005		0.001
328.50	330.00	D038336				1.50	<0.005		0.001
330.00	331.50	D038337				1.50	0.017		0.017
331.50	333.00	D038338				1.50	0.083		0.083
333.00	334.50	D038339				1.50	<0.005		0.001
334.50	336.00	D038340				1.50	0.129		0.129
336.00	337.50	D038341				1.50	0.176		0.176
337.50	339.00	D038342				1.50	0.875		0.875
339.00	340.50	D038344				1.50	0.201		0.201
340.50	342.00	D038345				1.50	0.007		0.007
342.00	343.50	D038346				1.50	0.021		0.021

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			343.50	345.00	D038347	1.50		0.060		0.060
			345.00	346.50	D038348	1.50		0.104		0.104
			346.50	348.00	D038349	1.50		0.012		0.012
			348.00	349.50	D038351	1.50		<0.005		0.001
			349.50	351.00	D038352	1.50		0.011		0.011
			351.00	352.50	D038354	1.50		<0.005		0.001
			352.50	354.00	D038355	1.50		0.028		0.028
			354.00	355.50	D038356	1.50		<0.005		0.001
			355.50	357.00	D038357	1.50		0.005		0.005
			357.00	358.50	D038358	1.50		0.008		0.008
			358.50	360.00	D038359	1.50		<0.005		0.001
			360.00	361.50	D038360	1.50		<0.005		0.001
			361.50	363.00	D038361	1.50		0.009		0.009
			363.00	364.50	D038362	1.50		0.045		0.045
			364.50	366.00	D038364	1.50		0.031		0.031
			366.00	367.50	D038365	1.50		<0.005		0.001
			367.50	368.50	D038366	1.00		0.011		0.011
			368.50	369.50	D038367	1.00		0.012		0.012
369.50	373.50	BA <b>Basalte</b> Basalte altéré en séricite et chlorite, contact progressif avec la syénite (altération), plusieurs amygdules, plusieurs grains de pyrite arrondis, quelques autres automorphes, plusieurs veines, veinules et cheveux carbonatés, ankérite.								
			369.50	370.80	D038368	1.30		0.011		0.011
		CH; SR <b>Chloriteux; Séricitique</b>	370.80	372.10	D038369	1.30		0.187		0.187
		Basalte séricitique et chloriteux.	372.10	373.50	D038370	1.40		0.079		0.079
373.50	437.00	SY <b>Syénite</b> Syénite hématisée, carbonatée et par endroits chloritisée, séricitisée et/ou silicifiée. Plusieurs phénocristaux généralement zonés (séricite, chlorite, hématite), plusieurs isométriques, d'autres avec les bords arrondis, magnétique presque continuellement entre environ 394 et 414.5 m. Pyrite très fine disséminée, séricite surtout sous forme de grains mais aussi dans plusieurs cheveux, veinules et veines, plusieurs cheveux chloritisés, beaucoup de grains d'ankérite et								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
373.50	437.00	quelques veines et veinules en contenant également. HM; CB; CH; SR; SI <b>Hématisé; Carbonaté; Chloriteux; Séricitique; Silicifié</b> Toutes les sortes d'altération sont présentes à des degrés différents, généralement fortement hématisé et faiblement to modérément carbonaté avec passages silicifiés, séricitisés et/ou chloritisés. Couleur très variable, de rosée à verdâtre ou grisâtre avec parfois des passages plus orangés ou beiges.	373.50	375.00	D038371	1.50	0.008		0.008
			375.00	376.50	D038372	1.50	<0.005		0.001
			376.50	378.00	D038374	1.50	<0.005		0.001
			378.00	378.90	D038375	0.90	0.047		0.047
			378.90	380.60	D038376	1.70	1.085		1.085
			380.60	382.00	D038377	1.40	0.027		0.027
			382.00	383.50	D038378	1.50	0.018		0.018
			383.50	385.00	D038379	1.50	0.104		0.104
			385.00	385.90	D038380	0.90	0.257		0.257
			385.90	386.80	D038381	0.90	0.115		0.115
			386.80	387.80	D038382	1.00	0.811		0.811
			387.80	388.80	D038384	1.00	0.925		0.925
			388.80	390.00	D038385	1.20	0.010		0.010
			390.00	391.50	D038386	1.50	0.019		0.019
			391.50	393.00	D038387	1.50	0.084		0.084
			393.00	394.50	D038388	1.50	0.013		0.013
			394.50	396.00	D038389	1.50	0.005		0.005
			396.00	397.50	D038391	1.50	0.008		0.008
			397.50	399.00	D038392	1.50	0.008		0.008
			399.00	400.50	D038394	1.50	0.005		0.005
			400.50	402.00	D038395	1.50	0.110		0.110
			402.00	403.50	D038396	1.50	0.020		0.020
			403.50	405.00	D038397	1.50	0.142		0.142
			405.00	406.50	D038398	1.50	<0.005		0.001
			406.50	408.00	D038399	1.50	0.155		0.155
			408.00	409.50	D038400	1.50	0.010		0.010
			409.50	411.00	D038401	1.50	0.032		0.032
			411.00	412.50	D038402	1.50	<0.005		0.001
			412.50	414.00	D038404	1.50	0.032		0.032
			414.00	415.50	D038405	1.50	<0.005		0.001
			415.50	417.00	D038406	1.50	<0.005		0.001
			417.00	418.50	D038407	1.50	<0.005		0.001
			418.50	420.00	D038408	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	420.00	421.50	D038409	1.50	0.297		0.297
	421.50	423.00	D038410	1.50	0.248		0.248
	423.00	424.50	D038411	1.50	0.010		0.010
	424.50	426.00	D038412	1.50	<0.005		0.001
	426.00	427.50	D038414	1.50	<0.005		0.001
	427.50	429.00	D038415	1.50	<0.005		0.001
	429.00	430.50	D038416	1.50	<0.005		0.001
	430.50	432.00	D038417	1.50	<0.005		0.001
	432.00	433.50	D038418	1.50	0.005		0.005
	433.50	435.00	D038419	1.50	<0.005		0.001
	435.00	436.00	D038420	1.00	<0.005		0.001
	436.00	437.00	D038421	1.00	<0.005		0.001
437.00	Fin du sondage Nombre d'échantillons : 303 Nombre d'échantillons QAQC : 42 Longueur totale échantillonnée : 434.80						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
5.00	5.00	D038080	M1	0.00	<0.005	0.001
23.00	23.00	D038093	J	0.00	0.732	0.732
36.50	38.00	D038103	D038102	1.50	0.026	0.026
44.50	44.50	D038110	M1	0.00	<0.005	0.001
47.50	47.50	D038113	K	0.00	0.920	0.920
59.50	61.00	D038123	D038122	1.50	0.019	0.019
73.00	73.00	D038133	L	0.00	2.320	2.320
86.50	88.00	D038143	D038142	1.50	0.157	0.157
94.50	94.50	D038150	M1	0.00	<0.005	0.001
96.60	96.60	D038153	M	0.00	3.220	3.220
108.00	109.50	D038163	D038162	1.50	1.765	1.765
121.50	121.50	D038173	J	0.00	0.774	0.774
135.00	136.50	D038183	D038182	1.50	0.016	0.016
142.40	142.40	D038190	M1	0.00	<0.005	0.001
145.50	145.50	D038193	K	0.00	1.070	1.070
159.00	160.50	D038203	D038202	1.50	0.006	0.006
171.00	171.00	D038213	L	0.00	2.320	2.320
184.50	186.00	D038223	D038222	1.50	<0.005	0.001
192.50	192.50	D038230	M1	0.00	<0.005	0.001
195.50	195.50	D038233	M	0.00	2.880	2.880
209.00	210.50	D038243	D038242	1.50	1.650	1.650
222.50	222.50	D038253	J	0.00	0.706	0.706
236.00	237.50	D038263	D038262	1.50	<0.005	0.001
245.00	245.00	D038270	M1	0.00	<0.005	0.001
248.00	248.00	D038273	K	0.00	0.924	0.924
260.50	262.00	D038283	D038282	1.50	<0.005	0.001
273.50	273.50	D038293	L	0.00	2.050	2.050
287.00	288.20	D038303	D038302	1.20	0.005	0.005
295.00	295.00	D038310	M1	0.00	0.009	0.009
298.00	298.00	D038313	M	0.00	3.060	3.060
311.50	313.00	D038323	D038322	1.50	0.625	0.625
324.00	324.00	D038333	J	0.00	0.783	0.783
337.50	339.00	D038343	D038342	1.50	0.879	0.879



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
346.50	346.50	D038350	M1	0.00	<0.005	0.001
349.50	349.50	D038353	K	0.00	1.020	1.020
363.00	364.50	D038363	D038362	1.50	0.045	0.045
375.00	375.00	D038373	L	0.00	2.130	2.130
386.80	387.80	D038383	D038382	1.00	0.807	0.807
394.50	394.50	D038390	M1	0.00	<0.005	0.001
397.50	397.50	D038393	M	0.00	3.010	3.010
411.00	412.50	D038403	D038402	1.50	<0.005	0.001
424.50	424.50	D038413	J	0.00	0.791	0.791

## Corporation Minière Osisko Div. Exploration

**Sondage :** BD10-220

Titre minier :

Section : 629900

Canton :

Niveau :

Foré par : Bradley

Rang :

Place de travail : Malartic

Décrit par : F. Larouche

Lot :

Du : 2010-05-08

Date de description : 2010-07-22

Au : 2010-05-12

Collet

UTM

Azimut : 0.00°  
Plongée : -60.00°  
Longueur : 350.00 m

Est	629 900.0
Nord	5 374 250.3
Élévation	279.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	45.00	0.00°	0.00°	Oui
Reflex	55.00	0.90°	-61.40°	Non
Reflex	65.00	0.90°	-61.60°	Non
Reflex	75.00	0.80°	-61.80°	Non
Reflex	85.00	1.00°	-62.00°	Non
Reflex	95.00	0.90°	-62.10°	Non
Reflex	105.00	0.90°	-62.30°	Non
Reflex	115.00	1.10°	-62.60°	Non
Reflex	125.00	1.20°	-62.70°	Non
Reflex	135.00	1.50°	-62.90°	Non
Reflex	145.00	1.80°	-63.10°	Non
Reflex	155.00	2.10°	-63.20°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	165.00	2.20°	-63.20°	Non
Reflex	175.00	2.50°	-63.30°	Non
Reflex	185.00	2.00°	-63.10°	Non
Reflex	195.00	1.70°	-62.70°	Non
Reflex	205.00	1.30°	-61.80°	Non
Reflex	215.00	2.70°	-61.70°	Non
Reflex	225.00	2.70°	-61.80°	Non
Reflex	235.00	2.40°	-61.80°	Non
Reflex	245.00	2.40°	-62.00°	Non
Reflex	255.00	2.60°	-62.00°	Non
Reflex	265.00	2.70°	-62.00°	Non
Reflex	275.00	2.90°	-62.00°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	42.00	MT <b>Mort-terrain</b>						
42.00	315.40	TU; BRC; POR <b>Tuf à cendre/lapillis 5°; Brèche de coulée; Porphyrique</b> Tuf à cristaux graphiteux, gris verdâtre, grains fins à moyens, des portions de qqes mètres sont bréchiqes (mcx de tuf dans une matrice graphiteuse), souvent porphyriques (porphyres de feldspaths), qqess vnls de Qz-Cb, 0.2 % Py (souvent associée au graphite), moy. alt. (CH), partiellement faib. alt. (CB)						
42.00	315.40	IN <b>Inaltéré</b>	42.00	43.00	D036755	1.00	<0.005	0.001
			43.00	44.00	D036756	1.00	<0.005	0.001
			44.00	45.50	D036757	1.50	<0.005	0.001
			45.50	47.00	D036759	1.50	<0.005	0.001
			47.00	48.50	D036760	1.50	<0.005	0.001
			48.50	50.00	D036761	1.50	<0.005	0.001
			50.00	51.50	D036762	1.50	<0.005	0.001
			51.50	53.00	D036763	1.50	<0.005	0.001
			53.00	54.50	D036764	1.50	<0.005	0.001
			54.50	56.00	D036765	1.50	<0.005	0.001
			56.00	57.50	D036766	1.50	0.006	0.006
			57.50	59.00	D036767	1.50	<0.005	0.001
			59.00	60.50	D036769	1.50	0.006	0.006
			60.50	62.00	D036770	1.50	<0.005	0.001
			62.00	63.50	D036771	1.50	<0.005	0.001
			63.50	65.00	D036772	1.50	<0.005	0.001
			65.00	66.50	D036773	1.50	<0.005	0.001
			66.50	68.00	D036774	1.50	0.005	0.005
			68.00	69.50	D036775	1.50	0.007	0.007
			69.50	71.00	D036776	1.50	<0.005	0.001
			71.00	72.50	D036777	1.50	<0.005	0.001
			72.50	74.00	D036779	1.50	<0.005	0.001
			74.00	75.50	D036781	1.50	<0.005	0.001
			75.50	77.00	D036782	1.50	<0.005	0.001
			77.00	78.50	D036783	1.50	<0.005	0.001
			78.50	80.00	D036784	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	80.00	81.50	D036785	1.50	<0.005		0.001
	81.50	83.00	D036786	1.50	0.005		0.005
	83.00	84.50	D036787	1.50	<0.005		0.001
	84.50	86.00	D036789	1.50	<0.005		0.001
	86.00	87.50	D036790	1.50	<0.005		0.001
	87.50	89.00	D036791	1.50	<0.005		0.001
	89.00	90.50	D036792	1.50	<0.005		0.001
	90.50	92.00	D036793	1.50	<0.005		0.001
	92.00	93.50	D036794	1.50	<0.005		0.001
	93.50	95.00	D036795	1.50	<0.005		0.001
	95.00	96.50	D036796	1.50	<0.005		0.001
	96.50	98.00	D036797	1.50	<0.005		0.001
	98.00	99.50	D036799	1.50	0.007		0.007
	99.50	101.00	D036800	1.50	0.016		0.016
	101.00	102.50	D036801	1.50	0.005		0.005
	102.50	104.00	D036802	1.50	<0.005		0.001
	104.00	105.50	D036803	1.50	<0.005		0.001
	105.50	107.00	D036804	1.50	<0.005		0.001
	107.00	108.50	D036805	1.50	<0.005		0.001
	108.50	110.00	D036806	1.50	<0.005		0.001
	110.00	111.50	D036807	1.50	0.007		0.007
	111.50	113.00	D036809	1.50	0.005		0.005
	113.00	114.50	D036810	1.50	<0.005		0.001
	114.50	116.00	D036811	1.50	<0.005		0.001
	116.00	117.50	D036812	1.50	<0.005		0.001
	117.50	119.00	D036813	1.50	<0.005		0.001
	119.00	120.50	D036814	1.50	<0.005		0.001
	120.50	122.00	D036815	1.50	<0.005		0.001
	122.00	123.50	D036816	1.50	<0.005		0.001
	123.50	125.00	D036817	1.50	<0.005		0.001
	125.00	126.50	D036819	1.50	<0.005		0.001
	126.50	128.00	D036821	1.50	0.006		0.006
	128.00	129.50	D036822	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	129.50	131.00	D036823	1.50	<0.005		0.001
	131.00	132.50	D036824	1.50	<0.005		0.001
	132.50	134.00	D036825	1.50	<0.005		0.001
	134.00	135.50	D036826	1.50	<0.005		0.001
	135.50	137.00	D036827	1.50	<0.005		0.001
	137.00	138.50	D036829	1.50	<0.005		0.001
	138.50	140.00	D036830	1.50	<0.005		0.001
	140.00	141.50	D036831	1.50	<0.005		0.001
	141.50	143.00	D036832	1.50	<0.005		0.001
	143.00	144.50	D036833	1.50	<0.005		0.001
	144.50	146.00	D036834	1.50	<0.005		0.001
	146.00	147.50	D036835	1.50	<0.005		0.001
	147.50	149.00	D036836	1.50	<0.005		0.001
	149.00	150.50	D036837	1.50	0.005		0.005
	150.50	152.00	D036839	1.50	<0.005		0.001
	152.00	153.50	D036840	1.50	<0.005		0.001
	153.50	155.00	D036841	1.50	<0.005		0.001
	155.00	156.50	D036842	1.50	<0.005		0.001
	156.50	158.00	D036843	1.50	<0.005		0.001
	158.00	159.50	D036844	1.50	<0.005		0.001
	159.50	161.00	D036845	1.50	<0.005		0.001
	161.00	162.50	D036846	1.50	0.008		0.008
	162.50	164.00	D036847	1.50	<0.005		0.001
	164.00	165.50	D036849	1.50	<0.005		0.001
	165.50	167.00	D036850	1.50	<0.005		0.001
	167.00	168.50	D036851	1.50	<0.005		0.001
	168.50	170.00	D036852	1.50	<0.005		0.001
	170.00	171.50	D036853	1.50	0.007		0.007
	171.50	173.00	D036854	1.50	<0.005		0.001
	173.00	174.50	D036855	1.50	<0.005		0.001
	174.50	176.00	D036856	1.50	<0.005		0.001
	176.00	177.50	D036857	1.50	<0.005		0.001
	177.50	179.00	D036859	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	179.00	180.70	D036861	1.70	<0.005		0.001
	180.70	182.00	D036862	1.30	<0.005		0.001
	182.00	183.50	D036863	1.50	<0.005		0.001
	183.50	185.00	D036864	1.50	<0.005		0.001
	185.00	186.50	D036865	1.50	<0.005		0.001
	186.50	188.00	D036866	1.50	<0.005		0.001
	188.00	189.50	D036867	1.50	<0.005		0.001
	189.50	191.00	D036869	1.50	<0.005		0.001
	191.00	192.50	D036870	1.50	<0.005		0.001
	192.50	194.00	D036871	1.50	<0.005		0.001
	194.00	195.50	D036872	1.50	<0.005		0.001
	195.50	197.00	D036873	1.50	<0.005		0.001
	197.00	198.50	D036874	1.50	<0.005		0.001
	198.50	200.00	D036875	1.50	<0.005		0.001
	200.00	201.50	D036876	1.50	<0.005		0.001
	201.50	203.00	D036877	1.50	<0.005		0.001
	203.00	204.50	D036879	1.50	<0.005		0.001
	204.50	206.00	D036880	1.50	<0.005		0.001
	206.00	207.50	D036881	1.50	<0.005		0.001
	207.50	209.00	D036882	1.50	0.007		0.007
	209.00	210.50	D036883	1.50	<0.005		0.001
	210.50	212.00	D036884	1.50	<0.005		0.001
	212.00	213.50	D036885	1.50	<0.005		0.001
	213.50	215.00	D036886	1.50	<0.005		0.001
	215.00	216.50	D036887	1.50	<0.005		0.001
	216.50	218.00	D036889	1.50	<0.005		0.001
	218.00	219.50	D036890	1.50	<0.005		0.001
	219.50	221.00	D036891	1.50	<0.005		0.001
	221.00	222.50	D036892	1.50	<0.005		0.001
	222.50	224.00	D036893	1.50	<0.005		0.001
	224.00	225.50	D036894	1.50	<0.005		0.001
	225.50	227.00	D036895	1.50	<0.005		0.001
	227.00	228.50	D036896	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	228.50	230.00	D036897	1.50	<0.005		0.001
	230.00	231.50	D036899	1.50	<0.005		0.001
	231.50	233.00	D036901	1.50	<0.005		0.001
	233.00	234.50	D036902	1.50	<0.005		0.001
	234.50	236.00	D036903	1.50	<0.005		0.001
	236.00	237.50	D036904	1.50	<0.005		0.001
	237.50	239.00	D036905	1.50	<0.005		0.001
	239.00	240.50	D036906	1.50	<0.005		0.001
	240.50	242.00	D036907	1.50	<0.005		0.001
	242.00	243.50	D036909	1.50	<0.005		0.001
	243.50	245.00	D036910	1.50	<0.005		0.001
	245.00	246.50	D036911	1.50	<0.005		0.001
	246.50	248.00	D036912	1.50	<0.005		0.001
	248.00	249.50	D036913	1.50	<0.005		0.001
	249.50	251.00	D036914	1.50	<0.005		0.001
	251.00	252.50	D036915	1.50	<0.005		0.001
	252.50	254.00	D036916	1.50	0.005		0.005
	254.00	255.50	D036917	1.50	<0.005		0.001
	255.50	257.00	D036919	1.50	0.006		0.006
	257.00	258.50	D036920	1.50	<0.005		0.001
	258.50	260.00	D036921	1.50	<0.005		0.001
	260.00	261.50	D036922	1.50	<0.005		0.001
	261.50	263.00	D036923	1.50	<0.005		0.001
	263.00	264.50	D036924	1.50	0.005		0.005
	264.50	266.00	D036925	1.50	<0.005		0.001
	266.00	267.50	D036926	1.50	<0.005		0.001
	267.50	269.00	D036927	1.50	0.005		0.005
	269.00	270.50	D036929	1.50	<0.005		0.001
	270.50	272.00	D036930	1.50	<0.005		0.001
	272.00	273.50	D036931	1.50	<0.005		0.001
	273.50	275.00	D036932	1.50	<0.005		0.001
	275.00	276.50	D036933	1.50	<0.005		0.001
	276.50	278.00	D036934	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			278.00	279.50	D036935	1.50	<0.005		0.001
			279.50	281.00	D036936	1.50	<0.005		0.001
			281.00	282.50	D036937	1.50	<0.005		0.001
			282.50	284.00	D036939	1.50	<0.005		0.001
			284.00	285.50	D036941	1.50	<0.005		0.001
			285.50	287.00	D036942	1.50	<0.005		0.001
			287.00	288.50	D036943	1.50	<0.005		0.001
			288.50	290.00	D036944	1.50	<0.005		0.001
			290.00	291.50	D036945	1.50	<0.005		0.001
			291.50	293.00	D036946	1.50	0.008		0.008
			293.00	294.50	D036947	1.50	0.008		0.008
			294.50	296.00	D036949	1.50	<0.005		0.001
			296.00	297.50	D036950	1.50	<0.005		0.001
			297.50	299.00	D036951	1.50	<0.005		0.001
			299.00	300.50	D036952	1.50	<0.005		0.001
			300.50	302.00	D036953	1.50	<0.005		0.001
			302.00	303.50	D036954	1.50	<0.005		0.001
			303.50	305.00	D036955	1.50	<0.005		0.001
			305.00	306.40	D036956	1.40	0.005		0.005
306.40	307.00	SY; POR	306.40	308.00	D036957	1.60	<0.005		0.001
		<b>Syénite; Porphyrique</b>	308.00	309.50	D036959	1.50	<0.005		0.001
		Syénite porphyrique "à latte", (porphyres feldspathiques	309.50	311.00	D036960	1.50	<0.005		0.001
		souvent automorphes, rectangulaires, allongés), gris verdâtre,	311.00	312.50	D036961	1.50	0.014		0.014
		grains moyens, présence de vnls de Qz-Cb, Tr. Py, contacts à	312.50	314.00	D036962	1.50	<0.005		0.001
		45° et - 45° AC	314.00	315.40	D036963	1.40	0.005		0.005
315.40	327.90	SY; POR							
		<b>Syénite 10°; Porphyrique</b>							
		Syénite porphyrique "à latte" (porphyres feldspathiques souvent							
		automorphes, rectangulaires, allongés), gris verdâtre, grains moyens,							
		présence de vnls de Qz-Cb, Tr. Py, Tr. Po (dans fractures), contacts							
		à 10° AC.							
315.40	327.90	CB	315.40	317.00	D036964	1.60	0.013		0.013
		<b>Carbonaté</b>	317.00	318.50	D036965	1.50	0.008		0.008
		Moy. alt. (CB)	318.50	320.00	D036966	1.50	0.015		0.015

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
327.90	350.00	TU; BRC; POR Tuf à cendre/lapillis; Brèche de coulée; Porphyrique Idem à: de 42.0 à 315.4 m	320.00	321.50	D036967	1.50	<0.005		0.001
			321.50	323.00	D036969	1.50	0.011		0.011
			323.00	324.50	D036970	1.50	0.025		0.025
			324.50	326.00	D036971	1.50	0.008		0.008
			326.00	327.00	D036972	1.00	0.005		0.005
			327.00	327.90	D036973	0.90	<0.005		0.001
			327.90	329.00	D036974	1.10	<0.005		0.001
327.90	350.00	IN Inaltéré	329.00	330.50	D036975	1.50	<0.005		0.001
			330.50	332.00	D036976	1.50	<0.005		0.001
			332.00	333.50	D036977	1.50	<0.005		0.001
			333.50	335.00	D036979	1.50	<0.005		0.001
			335.00	336.50	D036981	1.50	<0.005		0.001
			336.50	338.00	D036982	1.50	<0.005		0.001
			338.00	339.50	D036983	1.50	<0.005		0.001
			339.50	341.00	D036984	1.50	<0.005		0.001
			341.00	342.50	D036985	1.50	<0.005		0.001
			342.50	344.00	D036986	1.50	0.007		0.007
			344.00	345.50	D036987	1.50	<0.005		0.001
			345.50	347.00	D036989	1.50	<0.005		0.001
			347.00	348.50	D036990	1.50	0.005		0.005
			348.50	350.00	D036991	1.50	<0.005		0.001
350.00	Fin du sondage Nombre d'échantillons : 207 Nombre d'échantillons QAQC : 30 Longueur totale échantillonnée : 308.00								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
44.00	44.00	D036758	K	0.00	1.085	1.085
57.50	59.00	D036768	D036767	1.50	<0.005	0.001
71.00	71.00	D036778	L	0.00	2.240	2.240
72.50	72.50	D036780	M1	0.00	<0.005	0.001
83.00	84.50	D036788	D036787	1.50	<0.005	0.001
96.50	96.50	D036798	M	0.00	3.110	3.110
110.00	111.50	D036808	D036807	1.50	0.009	0.009
123.50	123.50	D036818	J	0.00	0.648	0.648
125.00	125.00	D036820	M1	0.00	<0.005	0.001
135.50	137.00	D036828	D036827	1.50	<0.005	0.001
149.00	149.00	D036838	K	0.00	1.130	1.130
162.50	164.00	D036848	D036847	1.50	0.007	0.007
176.00	176.00	D036858	L	0.00	2.080	2.080
177.50	177.50	D036860	M1	0.00	<0.005	0.001
188.00	189.50	D036868	D036867	1.50	<0.005	0.001
201.50	201.50	D036878	M	0.00	3.140	3.140
215.00	216.50	D036888	D036887	1.50	<0.005	0.001
228.50	228.50	D036898	J	0.00	0.745	0.745
230.00	230.00	D036900	M1	0.00	<0.005	0.001
240.50	242.00	D036908	D036907	1.50	<0.005	0.001
254.00	254.00	D036918	K	0.00	1.100	1.100
267.50	269.00	D036928	D036927	1.50	<0.005	0.001
281.00	281.00	D036938	L	0.00	2.240	2.240
282.50	282.50	D036940	M1	0.00	<0.005	0.001
293.00	294.50	D036948	D036947	1.50	<0.005	0.001
306.40	306.40	D036958	M	0.00	2.760	2.760
320.00	321.50	D036968	D036967	1.50	0.005	0.005
332.00	332.00	D036978	J	0.00	0.725	0.725
333.50	333.50	D036980	M1	0.00	<0.005	0.001
344.00	345.50	D036988	D036987	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	179.50°	-59.50°	Non					
Reflex	77.00	179.20°	-59.40°	Non					
Reflex	80.00	179.20°	-59.30°	Non					
Reflex	83.00	179.20°	-59.20°	Non					
Reflex	86.00	179.20°	-59.20°	Non					
Reflex	89.00	179.10°	-59.10°	Non					
Reflex	92.00	178.80°	-59.00°	Non					
Reflex	95.00	179.00°	-59.00°	Non					
Reflex	98.00	178.90°	-58.90°	Non					
Reflex	101.00	178.60°	-58.70°	Non					
Reflex	104.00	178.40°	-58.50°	Non					
Reflex	107.00	177.90°	-58.20°	Non					
Reflex	110.00	178.40°	-58.10°	Non					
Reflex	113.00	178.10°	-57.70°	Non					
Reflex	116.00	178.40°	-57.70°	Non					
Reflex	119.00	178.30°	-57.40°	Non					
Reflex	122.00	177.90°	-57.30°	Non					
Reflex	125.00	177.80°	-57.00°	Non					
Reflex	128.00	177.90°	-56.70°	Non					
Reflex	131.00	177.80°	-56.50°	Non					
Reflex	134.00	177.70°	-56.40°	Non					
Reflex	137.00	177.30°	-56.20°	Non					
Reflex	140.00	177.20°	-56.00°	Non					
Reflex	143.00	177.00°	-55.80°	Non					
Reflex	146.00	176.50°	-55.70°	Non					
Reflex	149.00	176.50°	-55.50°	Non					
Reflex	152.00	176.50°	-55.30°	Non					
Reflex	155.00	176.40°	-55.00°	Non					
Reflex	158.00	175.70°	-54.60°	Non					
Reflex	161.00	175.40°	-54.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	41.80	MT <b>Mort-terrain</b>						
41.80	52.90	DI <b>Diorite 65°</b> Diorite de couleur gris-pâle, carbonatée. Elle est foliée à 65°AC montré par les leucoxènes allongés. On voit encore les grains de FP et hornblende fins de 1 mm diam. Py en tr.						
41.80	57.00	CB30 <b>Carbonaté 30</b>	41.80	43.00	D032455	1.20	<0.005	0.001
			43.00	44.00	D032456	1.00	<0.005	0.001
			44.00	45.50	D032457	1.50	<0.005	0.001
			45.50	47.00	D032458	1.50	0.041	0.041
			47.00	48.50	D032459	1.50	<0.005	0.001
			48.50	50.00	D032460	1.50	<0.005	0.001
			50.00	51.50	D032461	1.50	<0.005	0.001
			51.50	52.90	D032462	1.40	<0.005	0.001
52.90	78.50	UM <b>Ultramafite serpentinisée 60°</b> Intensément foliées à 60°AC montrant de nombreux plissements. Plusieurs passages fortement fuschitisés et épidotisés. La roche est généralement molle avec une altération pervasive en talc. Fine Py disséminée inf. à 0.2%.  Elles sont carbonatées jusqu'à 57 m pour devenir par la suite non réactive au HCl. Cependant, on note plusieurs lamelles d'ankérite souvent en forme de cheveux entre les lamelles de UM foliées.	52.90	54.50	D032464	1.60	0.431	0.431
			54.50	56.00	D032465	1.50	0.169	0.169
			56.00	57.50	D032466	1.50	0.312	0.312
57.00	78.50	SR40 <b>Séricitique 40</b>	57.50	59.00	D032467	1.50	<0.005	0.001
			59.00	60.50	D032468	1.50	0.028	0.028
			60.50	62.00	D032469	1.50	<0.005	0.001
			62.00	63.50	D032470	1.50	<0.005	0.001
			63.50	65.00	D032472	1.50	<0.005	0.001
			65.00	66.50	D032473	1.50	<0.005	0.001
			66.50	68.00	D032474	1.50	<0.005	0.001
			68.00	69.50	D032475	1.50	<0.005	0.001
			69.50	71.00	D032476	1.50	<0.005	0.001
			71.00	72.50	D032477	1.50	<0.005	0.001
			72.50	74.00	D032478	1.50	0.079	0.079

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
78.50	95.80	UM; BR <b>Ultramafite serpentinisée; Bréchifié</b> Les UM sont id. aux précédentes mais sont extrêmement perturbées, plissées, schisteuses par endroits avec des boues de faille. Elles représentent probablement un couloir de déformation important.	74.00	75.50	D032479	1.50	0.012		0.012
			75.50	77.00	D032480	1.50	0.047		0.047
			77.00	78.50	D032481	1.50	0.030		0.030
			78.50	80.00	D032482	1.50	0.006		0.006
			80.00	81.50	D032484	1.50	<0.005		0.001
78.50	81.30	CIS <b>Cisaillement 50°</b>							
81.30	81.50	FAI <b>Faille</b> Boue de faille							
81.50	84.00	CIS <b>Cisaillement</b>	81.50	83.00	D032485	1.50	<0.005		0.001
			83.00	84.50	D032486	1.50	<0.005		0.001
84.00	85.00	FAI <b>Faille</b> Mauvaise récup et présence de boue	84.50	86.00	D032487	1.50	<0.005		0.001
85.00	93.50	CIS <b>Cisaillement</b>	86.00	87.50	D032488	1.50	<0.005		0.001
			87.50	89.00	D032489	1.50	<0.005		0.001
			89.00	90.50	D032490	1.50	<0.005		0.001
			90.50	92.00	D032491	1.50	<0.005		0.001
			92.00	93.50	D032492	1.50	0.013		0.013
93.50	93.60	FAI <b>Faille</b> boue	93.50	95.00	D032494	1.50	<0.005		0.001
93.60	95.80	CIS <b>Cisaillement</b>	95.00	96.50	D032495	1.50	<0.005		0.001
95.80	110.00	GR; CG <b>Grès 75°; Conglomérat</b> Unité gréseuse, homogène, à grains fins de 1 mm, chloritisée faible à moyen. Schistosité/litho bien développée à 75°AC.	96.50	98.00	D032496	1.50	0.013		0.013
			98.00	99.50	D032497	1.50	0.008		0.008
			99.50	101.00	D032498	1.50	0.016		0.016
			101.00	102.50	D032499	1.50	0.006		0.006
			102.50	104.00	D032500	1.50	0.006		0.006
			104.00	105.50	D032501	1.50	0.016		0.016
			105.50	107.00	D032502	1.50	0.008		0.008
107.00	108.50	D032504	1.50	0.008		0.008			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
110.00	156.60	<p>CG</p> <p><b>Conglomérat</b></p> <p>L'unité de conglomérat débute à 110 m montrant des cailloux polygéniques de grès, arénite, jaspe, porphyre, siltstone. Les galets sont plutôt grossiers de 110 à 143m, jusqu'à 8 cm et sont allongés dans la schisto à 55°AC.</p> <p>Les galets grisâtres (porphyre ?) sont pyritisés ainsi que ceux de jaspe.</p>	108.50	110.00	D032505	1.50	0.005		0.005
			110.00	111.50	D032506	1.50	0.005		0.005
			111.50	113.00	D032507	1.50	0.012		0.012
			113.00	114.50	D032508	1.50	0.138		0.138
			114.50	116.00	D032509	1.50	0.119		0.119
			116.00	117.50	D032510	1.50	0.078		0.078
			117.50	119.00	D032511	1.50	0.042		0.042
			119.00	120.50	D032512	1.50	0.195		0.195
			120.50	122.00	D032514	1.50	0.056		0.056
			122.00	123.50	D032515	1.50	0.130		0.130
			123.50	125.00	D032516	1.50	0.042		0.042
			125.00	126.50	D032517	1.50	0.059		0.059
			126.50	128.00	D032518	1.50	0.022		0.022
			128.00	129.50	D032519	1.50	0.024		0.024
			129.50	131.00	D032520	1.50	0.081		0.081
			131.00	132.50	D032522	1.50	0.017		0.017
			132.50	134.00	D032524	1.50	0.012		0.012
134.00	135.50	D032525	1.50	0.070		0.070			
135.50	137.00	D032526	1.50	0.009		0.009			
110.00	137.00	CB35							
		<b>Carbonaté 35</b>							
137.00	161.00	CB10	137.00	138.50	D032527	1.50	0.155		0.155
		<b>Carbonaté 10</b>	138.50	140.00	D032528	1.50	0.942		0.942
			140.00	141.50	D032529	1.50	0.113		0.113
			141.50	143.00	D032530	1.50	0.058		0.058
			143.00	144.50	D032531	1.50	0.052		0.052
			144.50	146.00	D032532	1.50	0.236		0.236
			146.00	147.50	D032534	1.50	0.163		0.163
			147.50	149.00	D032535	1.50	0.109		0.109
			149.00	150.50	D032536	1.50	0.087		0.087
			150.50	152.00	D032537	1.50	0.097		0.097
			152.00	153.50	D032538	1.50	0.029		0.029
			153.50	155.00	D032539	1.50	0.029		0.029



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
156.60	159.00	GR	155.00	156.60	D032540	1.60		0.031
		<b>Grès 65°</b>	156.60	158.00	D032541	1.40		0.011
		Id. au précédent. Plutôt chloritisé. Contact inf cisailé à 15°AC.	158.00	159.00	D032542	1.00		0.007
159.00	161.00	CG	159.00	160.00	D032544	1.00		0.021
		<b>Conglomérat 15°</b>	160.00	161.00	D032545	1.00		0.025
		Id. au précédent.						
		Fin du trou.						
161.00	Fin du sondage							
	Nombre d'échantillons : 81							
	Nombre d'échantillons QAQC : 10							
	Longueur totale échantillonnée : 119.20							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
51.50	51.50	D032463	J	0.00	0.681	0.681
62.00	62.00	D032471	M1	0.00	<0.005	0.001
78.50	78.50	D032483	K	0.00	1.010	1.010
92.00	93.50	D032493	D032492	1.50	0.011	0.011
105.50	105.50	D032503	L	0.00	2.050	2.050
119.00	120.50	D032513	D032512	1.50	0.225	0.225
129.50	129.50	D032521	M1	0.00	<0.005	0.001
131.00	131.00	D032523	M	0.00	2.810	2.810
144.50	146.00	D032533	D032532	1.50	0.222	0.222
158.00	158.00	D032543	J	0.00	0.808	0.808

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> BD10-222	Titre minier :	Section :	631000
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : A. Jean	Du : 2010-05-15	Date de description :	2010-06-16
	Au : 2010-05-18		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 334.50 m

UTM

Est	631 000.0
Nord	5 374 398.5
Élévation	312.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	1.20°	-58.80°	Non
Reflex	8.00	0.80°	-60.10°	Non
Reflex	11.00	359.40°	-59.30°	Non
Reflex	14.00	358.90°	-59.80°	Non
Reflex	17.00	359.30°	-59.70°	Non
Reflex	20.00	359.40°	-59.80°	Non
Reflex	23.00	359.50°	-59.70°	Non
Reflex	26.00	359.50°	-59.70°	Non
Reflex	29.00	359.40°	-59.70°	Non
Reflex	32.00	359.60°	-59.90°	Non
Reflex	35.00	359.70°	-59.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.90°	-59.80°	Non
Reflex	41.00	359.90°	-59.80°	Non
Reflex	44.00	359.80°	-59.90°	Non
Reflex	47.00	359.60°	-59.90°	Non
Reflex	50.00	359.40°	-59.90°	Non
Reflex	53.00	359.40°	-59.90°	Non
Reflex	56.00	359.20°	-59.90°	Non
Reflex	59.00	359.10°	-60.00°	Non
Reflex	62.00	359.00°	-59.90°	Non
Reflex	65.00	0.50°	-59.90°	Non
Reflex	68.00	1.40°	-59.90°	Oui
Reflex	71.00	0.60°	-59.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.00°	-59.80°	Non	Reflex	173.00	3.60°	-59.10°	Non
Reflex	77.00	0.80°	-59.80°	Non	Reflex	176.00	3.90°	-59.10°	Non
Reflex	80.00	1.00°	-59.80°	Non	Reflex	179.00	3.60°	-59.10°	Non
Reflex	83.00	1.00°	-59.90°	Non	Reflex	182.00	2.40°	-59.10°	Non
Reflex	86.00	359.80°	-59.80°	Non	Reflex	185.00	2.90°	-59.10°	Non
Reflex	89.00	1.20°	-59.80°	Non	Reflex	188.00	3.20°	-59.00°	Non
Reflex	92.00	1.90°	-59.80°	Non	Reflex	191.00	3.40°	-59.00°	Non
Reflex	95.00	1.70°	-59.80°	Non	Reflex	194.00	3.60°	-58.90°	Non
Reflex	98.00	358.90°	-59.80°	Non	Reflex	197.00	3.20°	-59.00°	Non
Reflex	101.00	359.00°	-59.80°	Non	Reflex	200.00	2.30°	-58.80°	Non
Reflex	104.00	0.60°	-59.80°	Non	Reflex	203.00	3.20°	-58.80°	Non
Reflex	107.00	1.10°	-59.70°	Non	Reflex	206.00	4.10°	-58.80°	Oui
Reflex	110.00	2.00°	-59.80°	Non	Reflex	209.00	2.60°	-58.80°	Non
Reflex	113.00	2.80°	-59.80°	Non	Reflex	212.00	1.90°	-58.80°	Non
Reflex	116.00	3.00°	-59.70°	Non	Reflex	215.00	2.80°	-58.60°	Non
Reflex	119.00	2.10°	-59.70°	Non	Reflex	218.00	2.40°	-58.60°	Non
Reflex	122.00	2.70°	-59.70°	Non	Reflex	221.00	2.10°	-58.40°	Non
Reflex	125.00	2.60°	-59.80°	Non	Reflex	224.00	3.10°	-58.20°	Non
Reflex	128.00	2.40°	-59.70°	Non	Reflex	227.00	3.00°	-58.20°	Non
Reflex	131.00	2.30°	-59.80°	Non	Reflex	230.00	3.60°	-58.20°	Non
Reflex	134.00	2.10°	-59.50°	Non	Reflex	233.00	0.60°	-58.20°	Oui
Reflex	137.00	2.20°	-59.60°	Non	Reflex	236.00	1.50°	-58.20°	Non
Reflex	140.00	1.90°	-59.30°	Non	Reflex	239.00	3.70°	-58.20°	Non
Reflex	143.00	1.70°	-59.40°	Non	Reflex	242.00	1.80°	-58.20°	Non
Reflex	146.00	1.80°	-59.40°	Non	Reflex	245.00	2.10°	-58.20°	Non
Reflex	149.00	1.10°	-59.40°	Non	Reflex	248.00	3.60°	-58.30°	Non
Reflex	152.00	2.90°	-59.40°	Non	Reflex	251.00	4.10°	-58.20°	Non
Reflex	155.00	2.50°	-59.30°	Non	Reflex	254.00	4.60°	-58.20°	Non
Reflex	158.00	2.20°	-59.20°	Non	Reflex	257.00	6.40°	-58.20°	Non
Reflex	161.00	2.10°	-59.10°	Non	Reflex	260.00	5.50°	-58.20°	Non
Reflex	164.00	2.20°	-59.00°	Non	Reflex	263.00	4.90°	-58.20°	Non
Reflex	167.00	3.10°	-59.10°	Oui	Reflex	266.00	4.80°	-58.20°	Non
Reflex	170.00	2.10°	-59.10°	Non	Reflex	269.00	5.20°	-58.20°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.70°	-58.10°	Non					
Reflex	275.00	0.90°	-58.10°	Oui					
Reflex	278.00	1.80°	-58.10°	Non					
Reflex	281.00	1.30°	-57.70°	Non					
Reflex	284.00	7.00°	-57.60°	Non					
Reflex	287.00	6.10°	-57.60°	Non					
Reflex	290.00	7.50°	-57.60°	Non					
Reflex	293.00	6.10°	-57.70°	Non					
Reflex	296.00	9.00°	-57.60°	Non					
Reflex	299.00	6.50°	-57.60°	Non					
Reflex	302.00	6.20°	-57.60°	Non					
Reflex	305.00	6.20°	-57.60°	Non					
Reflex	308.00	3.60°	-57.70°	Oui					
Reflex	311.00	4.80°	-57.70°	Non					
Reflex	314.00	5.80°	-57.70°	Non					
Reflex	317.00	3.50°	-57.60°	Non					
Reflex	320.00	3.70°	-57.60°	Non					
Reflex	323.00	4.80°	-57.60°	Non					
Reflex	326.00	3.20°	-57.60°	Non					
Reflex	329.00	3.40°	-57.70°	Non					
Reflex	332.00	3.30°	-57.70°	Non					
Reflex	334.50	3.60°	-58.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	3.00	MT						
		<b>Mort-terrain</b>						
3.00	334.50	SY;POR	3.00	4.00	D032001	1.00	0.268	0.268
		<b>Syénite; Porphyrique</b>	4.00	5.00	D032002	1.00	0.140	0.140
		De couleur très variable dûe à l'altération passant du rougeâtre au vert-grisâtre sur des longueurs décimétriques à qq mètres. Le % de	5.00	6.50	D032004	1.50	0.052	0.052
		Po de Fp est très variable passant de presque nul à 20-25% sur	6.50	8.00	D032005	1.50	0.219	0.219
		certaines sections métriques. La granulométrie de ceux-ci varie de 2	8.00	9.50	D032006	1.50	0.743	0.743
		mm à 1.5 cm et sont souvent prismatiques et fortement saussuritisées.	9.50	11.00	D032007	1.50	3.520	3.520
		Les premiers 50 m montrent beaucoup de fractures causant une forte	11.00	12.50	D032008	1.50	1.990	1.990
		oxydation de la roche soulignée par une couleur ocre intense.	12.50	14.00	D032009	1.50	1.350	1.350
		La minéralisation en sulfures ( Py + Asp + Galène) est très fine et	14.00	15.50	D032010	1.50	1.565	1.565
		difficilement observable à l'oeil nu. Le % de Py est faible, variant de	15.50	17.00	D032011	1.50	2.220	2.220
		0.2% à 0.4% alors que celui de l'Asp et Galène sont inférieurs à 0.1%.	17.00	18.50	D032012	1.50	1.835	1.835
		Le % de Py semble plus élevé dans la syénite gris-verdâtre (0.3 à	18.50	20.00	D032014	1.50	2.330	2.330
		0.4%) alors qu'il est plus faible dans la syénite rougeâtre (0.1 à 0.2%).	20.00	21.50	D032015	1.50	1.020	1.020
		La roche est passablement cataclasée et envahie par des carbonates	21.50	23.00	D032016	1.50	0.361	0.361
		(ankérite/sidérite/calcite) et ce jusqu'à 25% de la carotte.	23.00	24.50	D032017	1.50	0.086	0.086
		Fin du trou à 334.5m défoncé dans une ouverture minière.	24.50	26.00	D032018	1.50	0.688	0.688
3.00	51.90	HM50; CB40; SR20						
		<b>Hématisé 50; Carbonaté 40; Séricitique 20</b>						
		Altération très variable soulignée par les différentes couleurs,						
		passant du rougeâtre (hématisation) sur des longueurs						
		métriques au gris-verdâtre (séricitisation) sur des longueurs						
		dcm à métrique. Les changements de couleur sont fréquents						
		(jusqu'à 3 fois dans la même boîte).						
		La carbonatation est généralisée et occupe les interstices						
		entre les blocs cataclasés et aussi de nombreuses veinules mm						
		de ankérite et calcite.						
3.00	22.00	FRC						
		<b>Fracturé</b>						
25.50	29.40	FRC	26.00	27.50	D032019	1.50	1.015	1.015
		<b>Fracturé</b>	27.50	29.00	D032020	1.50	0.846	0.846
			29.00	30.50	D032021	1.50	0.752	0.752
			30.50	32.00	D032022	1.50	0.032	0.032

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
32.00      37.50 CIS <b>Cisaillement 65°</b> Les veinules de cb mm sont toutes alignées à 65°AC.	32.00	33.50	D032024	1.50	0.043		0.043	
	33.50	35.00	D032025	1.50	0.122		0.122	
	35.00	36.50	D032026	1.50	0.065		0.065	
	36.50	38.00	D032027	1.50	0.139		0.139	
	38.00	39.50	D032028	1.50	0.265		0.265	
	39.50	41.00	D032029	1.50	0.085		0.085	
	41.00	42.50	D032030	1.50	0.048		0.048	
	42.50	44.00	D032031	1.50	0.159		0.159	
	44.00	45.50	D032032	1.50	0.401		0.401	
	45.50	47.00	D032034	1.50	0.661		0.661	
	47.00	48.50	D032035	1.50	1.040		1.040	
	48.50	50.00	D032036	1.50	0.263		0.263	
	50.00	51.50	D032037	1.50	0.005		0.005	
	51.50	53.00	D032038	1.50	0.051		0.051	
	53.00	54.50	D032039	1.50	0.140		0.140	
	54.50	56.00	D032040	1.50	0.116		0.116	
	56.00	57.50	D032042	1.50	0.075		0.075	
	57.50	59.00	D032044	1.50	0.218		0.218	
	59.00	60.50	D032045	1.50	0.005		0.005	
	60.50	62.00	D032046	1.50	0.007		0.007	
	62.00	63.50	D032047	1.50	<0.005		0.001	
	63.50	65.00	D032048	1.50	0.040		0.040	
	65.00	66.50	D032049	1.50	<0.005		0.001	
	66.50	68.00	D032050	1.50	0.107		0.107	
	68.00	69.50	D032051	1.50	0.012		0.012	
	69.50	71.00	D032052	1.50	0.005		0.005	
	71.00	72.50	D032054	1.50	<0.005		0.001	
	72.50	74.00	D032055	1.50	0.007		0.007	
	74.00	75.50	D032056	1.50	<0.005		0.001	
75.50	77.00	D032057	1.50	0.038		0.038		
77.00	78.50	D032058	1.50	<0.005		0.001		
78.50	80.00	D032059	1.50	0.009		0.009		
80.00	81.50	D032060	1.50	0.015		0.015		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	81.50	83.00	D032061	1.50	0.011		0.011
	83.00	84.50	D032062	1.50	0.045		0.045
	84.50	86.00	D032064	1.50	0.017		0.017
	86.00	87.50	D032065	1.50	0.265		0.265
	87.50	89.00	D032066	1.50	0.014		0.014
	89.00	90.50	D032067	1.50	0.005		0.005
	90.50	92.00	D032068	1.50	<0.005		0.001
	92.00	93.50	D032069	1.50	0.008		0.008
	93.50	95.00	D032070	1.50	0.006		0.006
	95.00	96.50	D032071	1.50	<0.005		0.001
	96.50	98.00	D032072	1.50	<0.005		0.001
	98.00	99.50	D032074	1.50	<0.005		0.001
	99.50	101.00	D032075	1.50	<0.005		0.001
	101.00	102.50	D032076	1.50	0.019		0.019
	102.50	104.00	D032077	1.50	0.014		0.014
	104.00	105.50	D032078	1.50	0.032		0.032
	105.50	107.00	D032079	1.50	<0.005		0.001
	107.00	108.50	D032080	1.50	<0.005		0.001
	108.50	110.10	D032082	1.60	<0.005		0.001
	110.10	111.80	D032083	1.70	0.009		0.009
	111.80	113.00	D032084	1.20	0.006		0.006
	113.00	114.50	D032085	1.50	0.019		0.019
	114.50	116.00	D032086	1.50	0.011		0.011
	116.00	117.50	D032087	1.50	0.008		0.008
	117.50	119.00	D032088	1.50	0.011		0.011
118.50	136.30	CB20	D032089	1.50	<0.005		0.001
		<b>Carbonaté 20</b>	D032090	1.50	0.010		0.010
		Légère carbonatation pervasive sur l'ensemble de la syénite	D032091	1.50	0.016		0.016
		porphyrique. Les Po sont plus petits et moins nombreux. Mais la	D032092	1.50	0.095		0.095
		syénite est hématisée également soulignée par sa couleur	D032094	1.50	0.055		0.055
		rougeâtre	D032095	1.50	<0.005		0.001
			D032096	1.50	<0.005		0.001
			D032097	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			131.00	132.50	D032098	1.50	<0.005		0.001
			132.50	134.00	D032099	1.50	<0.005		0.001
			134.00	135.50	D032100	1.50	<0.005		0.001
			135.50	136.30	D032101	0.80	<0.005		0.001
136.30	137.40	CB75; SR50 <b>Carbonaté 75; Séricitique 50</b> Syénite verte, intensément séricitisée, cisailée et intensément carbonatée.	136.30	137.80	D032102	1.50	<0.005		0.001
137.40	138.80	SR50; CB20 <b>Séricitique 50; Carbonaté 20</b> Id. à la précédente mais la carbonatation est beaucoup moins intense	137.80	138.80	D032104	1.00	0.012		0.012
138.80	140.30	CB20 <b>Carbonaté 20</b> Id. à la précédente mais séricitisation très faible à nulle.	138.80	140.30	D032105	1.50	0.041		0.041
			140.30	141.50	D032106	1.20	0.597		0.597
			141.50	143.00	D032107	1.50	0.480		0.480
			143.00	144.50	D032108	1.50	0.569		0.569
			144.50	146.00	D032109	1.50	0.315		0.315
145.30	145.70	CIS; FRC <b>Cisaillement 65°; Fracturé</b> Zone tectonisée, bréchifiée et cisailée envahie par 2 v. qtz. La syénite est fortement séricitisée. 3% de Py dans la séricite.	146.00	147.50	D032110	1.50	<0.005		0.001
146.50	151.50	CB40 <b>Carbonaté 40</b> Carbonatation pervasive modérée de la syénite hématisée	147.50	149.00	D032111	1.50	<0.005		0.001
			149.00	150.50	D032112	1.50	0.754		0.754
			150.50	152.00	D032114	1.50	0.301		0.301
			152.00	153.20	D032115	1.20	<0.005		0.001
153.20	158.90	CB30 <b>Carbonaté 30</b> Carbonatation très variable passant de faible à intense sur des longueurs dcm.	153.20	154.70	D032116	1.50	<0.005		0.001
			154.70	156.40	D032117	1.70	<0.005		0.001
			156.40	157.40	D032118	1.00	<0.005		0.001
			157.40	158.90	D032119	1.50	0.019		0.019
158.90	162.30	SR30; CB30 <b>Séricitique 30; Carbonaté 30</b> Une séricitisation qui se rajoute à la syénite hématisée et carbonatée.	158.90	160.60	D032120	1.70	0.108		0.108
			160.60	162.30	D032122	1.70	0.056		0.056
162.30	163.60	VQ <b>Veine de Quartz massive 40°</b> Multiples veines de qtz fumé à 40°AC. La syénite est							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
162.30	163.60	SI25 <b>Silicifié 25</b> Silicification de la syénite cisailée combinée à des filons de qtz fumée d'épaisseur de 5-15 cm	162.30	163.60	D032124	1.30	0.992		0.992
163.60	165.90	CB30 <b>Carbonaté 30</b>	163.60	164.80	D032125	1.20	0.922		0.922
			164.80	165.90	D032126	1.10	0.713		0.713
165.90	171.10	SR25 <b>Séricitique 25</b> Syénite d'une couleur verte, d'aspect modérément bréchifiée.	165.90	167.00	D032127	1.10	4.400		4.400
			167.00	168.50	D032128	1.50	2.400		2.400
			168.50	170.00	D032129	1.50	2.160		2.160
			170.00	171.10	D032130	1.10	4.980		4.980
171.10	178.30	CB30 <b>Carbonaté 30</b> Très variable passant de faible à intense sur des longueurs dcm	171.10	172.50	D032131	1.40	0.041		0.041
			172.50	174.00	D032132	1.50	0.036		0.036
			174.00	175.50	D032134	1.50	0.063		0.063
			175.50	177.00	D032135	1.50	0.026		0.026
			177.00	178.30	D032136	1.30	0.005		0.005
178.30	180.20	SR30 <b>Séricitique 30</b>	178.30	179.30	D032137	1.00	0.008		0.008
			179.30	180.20	D032138	0.90	0.009		0.009
180.20	186.60	CB30 <b>Carbonaté 30</b> Très variable passant de faible à intense sur des longueurs dcm	180.20	181.50	D032139	1.30	0.065		0.065
			181.50	183.00	D032140	1.50	0.009		0.009
			183.00	184.50	D032141	1.50	0.011		0.011
			184.50	185.50	D032142	1.00	0.051		0.051
			185.50	186.60	D032144	1.10	0.011		0.011
186.60	187.30	QSSH <b>Schiste à qtz-séricite 30°</b> De couleur vert bouteille-fuschite, avec 25% de grains de Qtz sub-arrondis, 1-2 mm diam.							
186.60	187.30	SR40 <b>Séricitique 40</b>	186.60	187.30	D032145	0.70	0.008		0.008
187.30	190.10	CB20 <b>Carbonaté 20</b>	187.30	188.70	D032146	1.40	0.010		0.010
			188.70	190.10	D032147	1.40	0.005		0.005
190.10	190.70	QSSH <b>Schiste à qtz-séricite 40°</b> id. au précédent							
190.10	190.80	SR35	190.10	191.00	D032148	0.90	0.046		0.046

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
		<b>Séricitique 35</b>						
190.80	195.40	CB30	191.00	192.50	D032149	1.50	<0.005	0.001
		<b>Carbonaté 30</b>	192.50	194.00	D032150	1.50	<0.005	0.001
		Très variable passant de faible à intense sur des longueurs dcm	194.00	195.40	D032151	1.40	<0.005	0.001
195.40	195.70	QSSH						
		<b>Schiste à qtz-séricite 45°</b>						
		Id. aux 2 préc.						
195.40	197.30	SR40	195.40	197.00	D032152	1.60	<0.005	0.001
		<b>Séricitique 40</b>	197.00	198.50	D032154	1.50	<0.005	0.001
197.30	206.00	CB25	198.50	200.00	D032155	1.50	<0.005	0.001
		<b>Carbonaté 25</b>	200.00	201.50	D032156	1.50	<0.005	0.001
		Très variable passant de faible à intense sur des longueurs dcm						
201.50	201.70	QSSH	201.50	203.00	D032157	1.50	0.158	0.158
		<b>Schiste à qtz-séricite 30°</b>	203.00	204.50	D032158	1.50	0.260	0.260
		Id. aux 3 préc.	204.50	206.00	D032159	1.50	<0.005	0.001
206.00	220.00	CB10	206.00	207.50	D032160	1.50	<0.005	0.001
		<b>Carbonaté 10</b>	207.50	209.00	D032162	1.50	0.005	0.005
		Carbonatation variable mais plutôt faible	209.00	210.50	D032164	1.50	0.012	0.012
			210.50	212.00	D032165	1.50	<0.005	0.001
			212.00	212.80	D032166	0.80	0.006	0.006
212.80	213.60	INMA	212.80	213.60	D032167	0.80	0.006	0.006
		<b>Intrusion mafique (dyke) 30°</b>	213.60	215.00	D032168	1.40	0.038	0.038
		Dyke mafique de composition andésitique aux contacts nets à 30°AC						
214.60	214.90	VQ	215.00	216.50	D032169	1.50	0.007	0.007
		<b>Veine de Quartz massive 45°</b>	216.50	218.00	D032170	1.50	0.031	0.031
		Avec cb, fortement hématisée	218.00	219.50	D032171	1.50	0.035	0.035
			219.50	220.30	D032172	0.80	0.052	0.052
220.00	275.00	CB50						
		<b>Carbonaté 50</b>						
		Carbonatation modérée à intense sur certains passages dcm.						
220.30	221.60	INMA	220.30	221.60	D032174	1.30	0.026	0.026
		<b>Intrusion mafique (dyke) 75°</b>	221.60	222.80	D032175	1.20	0.005	0.005
		id. au précédent	222.80	224.00	D032176	1.20	0.005	0.005
			224.00	225.50	D032177	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
230.25	230.65	INMA; VQ <b>Intrusion mafique (dyke) 30°; Veine de Quartz massive</b> Intrusion mafique accompagnée d'une V de Qtz-Cb-To irrégulière.	225.50	227.00	D032178	1.50	0.011		0.011
			227.00	228.50	D032179	1.50	0.005		0.005
			228.50	230.00	D032180	1.50	0.008		0.008
			230.00	231.50	D032181	1.50	0.007		0.007
			231.50	233.00	D032182	1.50	0.005		0.005
			233.00	234.50	D032184	1.50	0.008		0.008
			234.50	236.00	D032185	1.50	0.005		0.005
			236.00	237.50	D032186	1.50	0.005		0.005
			237.50	239.00	D032187	1.50	<0.005		0.001
			239.00	240.50	D032188	1.50	<0.005		0.001
			240.50	242.00	D032189	1.50	<0.005		0.001
			242.00	243.50	D032190	1.50	0.258		0.258
			242.40	243.20	INMA; VQ <b>Intrusion mafique (dyke) 35°; Veine de Quartz massive</b> Filon de calcite rose combinée à une veine de qtz	243.50	245.00	D032191	1.50
245.00	246.50	D032192				1.50	0.028		0.028
246.50	248.00	D032194				1.50	0.177		0.177
248.00	249.50	D032195				1.50	0.337		0.337
249.50	251.00	D032196				1.50	0.007		0.007
251.00	252.50	D032197				1.50	0.006		0.006
252.50	254.00	D032198				1.50	0.030		0.030
254.00	255.50	D032199				1.50	0.014		0.014
255.50	257.00	D032200				1.50	0.011		0.011
256.10	256.70	VQ <b>Veine de Quartz massive 15°</b> Avec cb, env. 3 cm ép				257.00	258.50	D032202	1.50
			258.50	260.00	D032204	1.50	0.009		0.009
			260.00	261.50	D032205	1.50	0.006		0.006
			261.50	263.00	D032206	1.50	0.009		0.009
			263.00	264.50	D032207	1.50	0.008		0.008
			264.50	266.00	D032208	1.50	0.006		0.006
			266.00	267.50	D032209	1.50	0.022		0.022
			267.50	269.00	D032210	1.50	0.015		0.015
			269.00	270.50	D032211	1.50	<0.005		0.001
			270.50	272.00	D032212	1.50	0.087		0.087
272.00	273.50	D032214	1.50	0.443		0.443			
273.50	275.00	D032215	1.50	0.035		0.035			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
275.00	281.00	SR35 <b>Séricitique 35</b> Apparance d'un schiste à séricite par endroits.	275.00	276.50	D032216	1.50	0.089		0.089
			276.50	278.00	D032217	1.50	0.194		0.194
			278.00	279.50	D032218	1.50	0.143		0.143
			279.50	281.00	D032219	1.50	0.509		0.509
281.00	327.50	CB50 <b>Carbonaté 50</b>	281.00	282.50	D032220	1.50	0.165		0.165
			282.50	284.00	D032221	1.50	0.052		0.052
			284.00	285.50	D032222	1.50	0.104		0.104
			285.50	287.00	D032224	1.50	<0.005		0.001
			287.00	288.50	D032225	1.50	0.008		0.008
			288.50	290.00	D032226	1.50	<0.005		0.001
			290.00	291.50	D032227	1.50	<0.005		0.001
			291.50	293.00	D032228	1.50	0.017		0.017
			293.00	294.50	D032229	1.50	0.010		0.010
			294.50	296.00	D032230	1.50	<0.005		0.001
			296.00	297.50	D032231	1.50	0.005		0.005
			297.50	299.00	D032232	1.50	0.013		0.013
			299.00	300.50	D032234	1.50	<0.005		0.001
			300.50	302.00	D032235	1.50	<0.005		0.001
			302.00	303.50	D032236	1.50	<0.005		0.001
			303.50	305.00	D032237	1.50	0.252		0.252
			305.00	306.50	D032238	1.50	<0.005		0.001
			306.50	308.00	D032239	1.50	0.027		0.027
			308.00	309.50	D032240	1.50	0.008		0.008
			309.50	311.00	D032242	1.50	<0.005		0.001
311.00	312.50	D032244	1.50	<0.005		0.001			
312.50	314.00	D032245	1.50	<0.005		0.001			
314.00	315.50	D032246	1.50	<0.005		0.001			
315.50	317.00	D032247	1.50	0.216		0.216			
317.00	318.50	D032248	1.50	0.055		0.055			
318.50	320.00	D032249	1.50	0.118		0.118			
320.00	321.50	D032250	1.50	0.294		0.294			
321.50	323.00	D032251	1.50	0.212		0.212			
323.00	324.50	D032252	1.50	0.089		0.089			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
327.50	332.00	BL35 <b>Potassique blanchi 35</b> Protolite de syénite mais d'aspect blanchie et lessivée. Absence de carbonatation.	324.50	326.00	D032254	1.50	0.423		0.423
			326.00	327.50	D032255	1.50	0.347		0.347
			327.50	329.00	D032256	1.50	0.412		0.412
			329.00	330.50	D032257	1.50	0.256		0.256
			330.50	332.00	D032258	1.50	0.225		0.225
332.00	334.50	CB50 <b>Carbonaté 50</b>	332.00	333.50	D032259	1.50	0.434		0.434
			333.50	334.50	D032260	1.00	0.213		0.213
334.50 Fin du sondage Nombre d'échantillons : 229 Nombre d'échantillons QAQC : 31 Longueur totale échantillonnée : 331.50									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.00	4.00	D032003	K	0.00	1.180	1.180
17.00	18.50	D032013	D032012	1.50	1.585	1.585
30.50	30.50	D032023	L	0.00	2.450	2.450
44.00	45.50	D032033	D032032	1.50	0.403	0.403
54.50	54.50	D032041	M1	0.00	0.013	0.013
56.00	56.00	D032043	M	0.00	3.190	3.190
69.50	71.00	D032053	D032052	1.50	0.031	0.031
83.00	83.00	D032063	J	0.00	0.842	0.842
96.50	98.00	D032073	D032072	1.50	<0.005	0.001
107.00	107.00	D032081	M1	0.00	<0.005	0.001
123.50	125.00	D032093	D032092	1.50	0.080	0.080
136.30	136.30	D032103	L	0.00	2.180	2.180
149.00	150.50	D032113	D032112	1.50	0.642	0.642
158.90	158.90	D032121	M1	0.00	<0.005	0.001
160.60	160.60	D032123	M	0.00	3.020	3.020
172.50	174.00	D032133	D032132	1.50	0.038	0.038
184.50	184.50	D032143	J	0.00	0.771	0.771
195.40	197.00	D032153	D032152	1.60	<0.005	0.001
206.00	206.00	D032161	M1	0.00	<0.005	0.001
207.50	207.50	D032163	K	0.00	1.000	1.000
219.50	220.30	D032173	D032172	0.80	0.054	0.054
231.50	231.50	D032183	L	0.00	2.060	2.060
245.00	246.50	D032193	D032192	1.50	0.023	0.023
255.50	255.50	D032201	M1	0.00	0.005	0.005
257.00	257.00	D032203	M	0.00	2.950	2.950
270.50	272.00	D032213	D032212	1.50	0.074	0.074
284.00	284.00	D032223	J	0.00	0.757	0.757
297.50	299.00	D032233	D032232	1.50	0.015	0.015
308.00	308.00	D032241	M1	0.00	<0.005	0.001
309.50	309.50	D032243	K	0.00	1.060	1.060
323.00	324.50	D032253	D032252	1.50	0.091	0.091

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-223**

Titre minier :

Section :                      630700

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy Gbaguidi

Lot :

Du :                      2010-05-17

Date de description :

Au :                      2010-05-23

Collet

UTM

Azimut :                      0.00°

Plongée :                      -60.00°

Longueur :                      483.00 m

Est                              630 700.1

Nord                              5 374 251.6

Élévation                      314.1

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	0.00	0.00°	0.00°	Oui
Reflex	3.00	98.40°	0.60°	Oui
Reflex	6.00	148.20°	0.60°	Oui
Reflex	9.00	3.20°	-59.80°	Non
Reflex	12.00	4.30°	-59.90°	Non
Reflex	15.00	4.30°	-60.10°	Non
Reflex	18.00	3.20°	-60.00°	Non
Reflex	21.00	2.50°	-60.00°	Non
Reflex	24.00	1.50°	-60.00°	Non
Reflex	27.00	1.70°	-59.90°	Non
Reflex	30.00	0.80°	-59.90°	Non
Reflex	33.00	1.90°	-59.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	36.00	1.60°	-60.00°	Non
Reflex	39.00	2.20°	-59.90°	Non
Reflex	42.00	2.40°	-60.10°	Non
Reflex	45.00	1.30°	-60.10°	Non
Reflex	48.00	1.20°	-59.80°	Non
Reflex	51.00	358.80°	-58.40°	Non
Reflex	54.00	359.80°	-59.80°	Non
Reflex	57.00	0.90°	-60.10°	Non
Reflex	60.00	0.60°	-59.40°	Non
Reflex	63.00	0.20°	-58.30°	Non
Reflex	66.00	1.10°	-59.90°	Non
Reflex	69.00	1.30°	-59.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	72.00	1.10°	-60.70°	Non
Reflex	75.00	1.10°	-59.80°	Non
Reflex	78.00	1.50°	-59.80°	Non
Reflex	81.00	0.70°	-60.10°	Non
Reflex	84.00	1.10°	-58.90°	Non
Reflex	87.00	3.50°	-60.00°	Non
Reflex	90.00	3.90°	-60.00°	Non
Reflex	93.00	2.10°	-58.50°	Non
Reflex	96.00	2.00°	-60.00°	Non
Reflex	99.00	3.50°	-60.20°	Non
Reflex	102.00	4.50°	-60.30°	Non
Reflex	105.00	4.40°	-60.30°	Non
Reflex	108.00	1.70°	-60.20°	Oui
Reflex	111.00	2.40°	-60.20°	Oui
Reflex	114.00	4.40°	-60.30°	Non
Reflex	117.00	4.50°	-60.40°	Non
Reflex	120.00	4.90°	-60.30°	Non
Reflex	123.00	2.60°	-60.20°	Oui
Reflex	126.00	5.20°	-60.40°	Non
Reflex	129.00	4.00°	-60.30°	Non
Reflex	132.00	5.20°	-60.40°	Non
Reflex	135.00	2.40°	-60.30°	Oui
Reflex	138.00	3.00°	-60.30°	Oui
Reflex	141.00	4.10°	-60.30°	Non
Reflex	144.00	3.70°	-60.30°	Non
Reflex	147.00	3.80°	-60.20°	Non
Reflex	150.00	2.70°	-60.20°	Oui
Reflex	153.00	5.60°	-60.40°	Non
Reflex	156.00	3.00°	-60.10°	Oui
Reflex	159.00	4.20°	-60.00°	Non
Reflex	162.00	4.90°	-60.10°	Non
Reflex	165.00	4.60°	-60.00°	Non
Reflex	168.00	3.50°	-60.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	171.00	3.50°	-59.90°	Non
Reflex	174.00	4.70°	-59.80°	Non
Reflex	177.00	7.80°	-59.80°	Oui
Reflex	180.00	5.20°	-59.60°	Non
Reflex	183.00	8.10°	-59.80°	Non
Reflex	186.00	8.50°	-59.70°	Non
Reflex	189.00	7.50°	-59.40°	Non
Reflex	192.00	5.60°	-59.30°	Oui
Reflex	195.00	6.60°	-59.30°	Non
Reflex	198.00	7.80°	-59.40°	Non
Reflex	201.00	6.90°	-59.40°	Non
Reflex	204.00	5.30°	-59.30°	Oui
Reflex	207.00	7.10°	-59.60°	Non
Reflex	210.00	8.10°	-59.50°	Non
Reflex	213.00	6.90°	-59.40°	Oui
Reflex	216.00	9.10°	-59.50°	Non
Reflex	219.00	10.30°	-59.60°	Non
Reflex	222.00	9.80°	-59.50°	Non
Reflex	225.00	7.60°	-59.40°	Non
Reflex	228.00	5.40°	-59.50°	Oui
Reflex	231.00	8.60°	-59.60°	Non
Reflex	234.00	9.60°	-59.60°	Non
Reflex	237.00	9.20°	-59.60°	Non
Reflex	240.00	8.50°	-59.50°	Non
Reflex	243.00	9.90°	-59.50°	Non
Reflex	246.00	8.60°	-59.30°	Non
Reflex	249.00	7.90°	-59.10°	Oui
Reflex	252.00	9.90°	-59.30°	Non
Reflex	255.00	7.70°	-59.20°	Non
Reflex	258.00	7.10°	-59.10°	Non
Reflex	261.00	7.30°	-59.20°	Non
Reflex	264.00	9.00°	-59.30°	Oui
Reflex	267.00	7.10°	-59.20°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	270.00	8.80°	-59.20°	Non
Reflex	273.00	6.70°	-59.10°	Oui
Reflex	276.00	7.20°	-59.10°	Non
Reflex	279.00	8.10°	-59.10°	Non
Reflex	282.00	6.00°	-59.00°	Non
Reflex	285.00	6.70°	-58.90°	Non
Reflex	288.00	6.40°	-59.00°	Non
Reflex	291.00	6.30°	-58.90°	Non
Reflex	294.00	9.00°	-58.80°	Oui
Reflex	297.00	7.90°	-58.70°	Non
Reflex	300.00	8.40°	-58.70°	Non
Reflex	303.00	8.10°	-58.60°	Non
Reflex	306.00	7.50°	-58.50°	Non
Reflex	309.00	8.20°	-58.40°	Non
Reflex	312.00	9.40°	-58.40°	Non
Reflex	315.00	7.50°	-58.30°	Non
Reflex	318.00	7.70°	-58.20°	Non
Reflex	321.00	10.90°	-58.30°	Non
Reflex	324.00	10.10°	-58.10°	Non
Reflex	327.00	9.80°	-58.00°	Non
Reflex	330.00	10.90°	-57.80°	Non
Reflex	333.00	8.50°	-57.50°	Oui
Reflex	336.00	10.60°	-57.60°	Non
Reflex	339.00	9.80°	-57.60°	Non
Reflex	342.00	10.10°	-57.60°	Non
Reflex	345.00	10.20°	-57.80°	Non
Reflex	348.00	7.90°	-57.60°	Non
Reflex	351.00	7.60°	-57.60°	Non
Reflex	354.00	7.80°	-57.40°	Non
Reflex	357.00	8.70°	-57.40°	Non
Reflex	360.00	10.50°	-57.30°	Non
Reflex	363.00	7.50°	-57.10°	Oui
Reflex	366.00	11.90°	-57.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	369.00	11.00°	-57.00°	Non
Reflex	372.00	8.80°	-56.70°	Oui
Reflex	375.00	10.50°	-56.60°	Non
Reflex	378.00	10.10°	-56.40°	Non
Reflex	381.00	10.60°	-56.30°	Non
Reflex	384.00	9.20°	-56.10°	Non
Reflex	387.00	8.90°	-56.00°	Oui
Reflex	390.00	25.90°	-63.20°	Oui
Reflex	393.00	11.50°	-55.90°	Non
Reflex	396.00	11.50°	-55.80°	Non
Reflex	399.00	9.30°	-55.70°	Non
Reflex	402.00	10.30°	-55.50°	Non
Reflex	405.00	11.30°	-55.50°	Non
Reflex	408.00	12.60°	-55.30°	Non
Reflex	411.00	9.60°	-55.10°	Oui
Reflex	414.00	12.50°	-55.20°	Non
Reflex	417.00	10.70°	-54.90°	Oui
Reflex	420.00	12.70°	-54.90°	Non
Reflex	423.00	7.40°	-54.70°	Oui
Reflex	426.00	10.70°	-54.60°	Non
Reflex	429.00	10.60°	-54.60°	Non
Reflex	432.00	13.30°	-54.40°	Oui
Reflex	435.00	10.20°	-54.20°	Non
Reflex	438.00	12.30°	-54.30°	Non
Reflex	441.00	10.20°	-54.10°	Non
Reflex	444.00	9.80°	-54.00°	Oui
Reflex	447.00	12.00°	-53.80°	Oui
Reflex	450.00	10.10°	-53.70°	Non
Reflex	453.00	11.60°	-53.60°	Non
Reflex	456.00	10.00°	-53.40°	Non
Reflex	459.00	11.40°	-53.40°	Non
Reflex	462.00	9.90°	-53.10°	Non
Reflex	465.00	9.30°	-53.00°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	468.00	9.40°	-52.90°	Non					
Reflex	471.00	11.60°	-52.80°	Non					
Reflex	474.00	13.10°	-52.80°	Oui					
Reflex	477.00	12.40°	-52.60°	Non					
Reflex	480.00	13.70°	-52.40°	Non					
Reflex	483.00	13.00°	-52.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.30	MT						
		<b>Mort-terrain</b>						
2.30	483.00	SY; POR	2.30	4.00	D022724	1.70	0.005	0.005
		<b>Syénite; Porphyrique</b>						
		Syénite porphyrique hématisée, séricitisée, localement magnétique.						
			4.00	5.50	D022725	1.50	<0.005	0.001
			5.50	7.00	D022726	1.50	<0.005	0.001
			7.00	8.50	D022727	1.50	0.005	0.005
			8.50	10.00	D022728	1.50	<0.005	0.001
			10.00	11.50	D022729	1.50	<0.005	0.001
			11.50	13.00	D022730	1.50	<0.005	0.001
			13.00	14.50	D022731	1.50	<0.005	0.001
			14.50	16.00	D022732	1.50	<0.005	0.001
			16.00	17.50	D022733	1.50	<0.005	0.001
			17.50	19.00	D022734	1.50	<0.005	0.001
			19.00	20.50	D022736	1.50	<0.005	0.001
			20.50	22.00	D022737	1.50	0.006	0.006
			22.00	23.50	D022738	1.50	<0.005	0.001
			23.50	25.00	D022739	1.50	<0.005	0.001
			25.00	26.50	D022740	1.50	<0.005	0.001
			26.50	28.00	D022741	1.50	<0.005	0.001
			28.00	29.50	D022742	1.50	<0.005	0.001
			29.50	31.00	D022743	1.50	<0.005	0.001
			31.00	32.50	D022744	1.50	0.070	0.070
			32.50	34.00	D022746	1.50	<0.005	0.001
			34.00	35.50	D022747	1.50	<0.005	0.001
			35.50	37.00	D022748	1.50	<0.005	0.001
			37.00	38.00	D022749	1.00	<0.005	0.001
			38.00	39.50	D022750	1.50	<0.005	0.001
			39.50	41.00	D022751	1.50	0.008	0.008
			41.00	42.50	D022752	1.50	<0.005	0.001
			42.50	44.00	D022753	1.50	<0.005	0.001
			44.00	45.50	D022754	1.50	<0.005	0.001
			45.50	47.00	D022756	1.50	<0.005	0.001
			47.00	48.50	D022757	1.50	0.005	0.005
			48.50	50.00	D022758	1.50	0.064	0.064

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	50.00	51.50	D022759	1.50	0.026		0.026
	51.50	53.00	D022761	1.50	<0.005		0.001
	53.00	54.50	D022762	1.50	<0.005		0.001
	54.50	56.00	D022763	1.50	0.009		0.009
	56.00	57.50	D022764	1.50	0.010		0.010
	57.50	59.00	D022766	1.50	<0.005		0.001
	59.00	60.50	D022767	1.50	0.008		0.008
	60.50	62.00	D022768	1.50	<0.005		0.001
	62.00	63.50	D022769	1.50	<0.005		0.001
	63.50	65.00	D022770	1.50	<0.005		0.001
	65.00	66.50	D022771	1.50	<0.005		0.001
	66.50	68.00	D022772	1.50	0.186		0.186
	68.00	69.50	D022773	1.50	0.016		0.016
	69.50	71.00	D022774	1.50	<0.005		0.001
	71.00	72.50	D022776	1.50	0.058		0.058
	72.50	74.00	D022777	1.50	0.118		0.118
	74.00	75.50	D022778	1.50	0.158		0.158
	75.50	77.00	D022779	1.50	0.012		0.012
	77.00	78.50	D022780	1.50	<0.005		0.001
	78.50	80.00	D022781	1.50	0.008		0.008
	80.00	81.50	D022782	1.50	0.009		0.009
	81.50	83.00	D022783	1.50	0.039		0.039
	83.00	84.50	D022784	1.50	0.020		0.020
	84.50	86.00	D022786	1.50	0.011		0.011
	86.00	87.50	D022787	1.50	0.043		0.043
	87.50	89.00	D022788	1.50	0.103		0.103
	89.00	90.50	D022789	1.50	0.034		0.034
	90.50	92.00	D022790	1.50	0.007		0.007
	92.00	93.50	D022791	1.50	<0.005		0.001
	93.50	95.00	D022792	1.50	<0.005		0.001
	95.00	96.50	D022793	1.50	<0.005		0.001
	96.50	98.00	D022794	1.50	<0.005		0.001
	98.00	99.50	D022796	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	99.50	101.00	D022797	1.50	<0.005		0.001
	101.00	102.50	D022798	1.50	<0.005		0.001
	102.50	104.00	D022799	1.50	<0.005		0.001
	104.00	105.50	D022801	1.50	<0.005		0.001
	105.50	107.00	D022802	1.50	<0.005		0.001
	107.00	108.50	D022803	1.50	0.011		0.011
	108.50	110.00	D022804	1.50	<0.005		0.001
	110.00	111.50	D022806	1.50	0.005		0.005
	111.50	113.00	D022807	1.50	<0.005		0.001
	113.00	114.50	D022808	1.50	<0.005		0.001
	114.50	116.00	D022809	1.50	<0.005		0.001
	116.00	117.50	D022810	1.50	<0.005		0.001
	117.50	119.00	D022811	1.50	<0.005		0.001
	119.00	120.50	D022812	1.50	<0.005		0.001
	120.50	122.00	D022813	1.50	<0.005		0.001
	122.00	123.50	D022814	1.50	0.005		0.005
	123.50	125.00	D022816	1.50	<0.005		0.001
	125.00	126.50	D022817	1.50	<0.005		0.001
	126.50	128.00	D022818	1.50	<0.005		0.001
	128.00	129.50	D022819	1.50	<0.005		0.001
	129.50	131.00	D022820	1.50	<0.005		0.001
	131.00	132.50	D022821	1.50	<0.005		0.001
	132.50	134.00	D022822	1.50	<0.005		0.001
	134.00	135.50	D022823	1.50	<0.005		0.001
	135.50	137.00	D022824	1.50	<0.005		0.001
	137.00	138.50	D022826	1.50	0.276		0.276
	138.50	140.00	D022827	1.50	0.008		0.008
	140.00	141.00	D022828	1.00	0.025		0.025
	141.00	142.50	D022829	1.50	0.243		0.243
	142.50	144.00	D022830	1.50	<0.005		0.001
	144.00	145.50	D022831	1.50	<0.005		0.001
	145.50	147.00	D022832	1.50	0.362		0.362
	147.00	148.50	D022833	1.50	0.178		0.178

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.50	150.00	D022834	1.50	0.029		0.029
	150.00	151.50	D022836	1.50	<0.005		0.001
	151.50	153.00	D022837	1.50	0.006		0.006
	153.00	154.50	D022838	1.50	0.074		0.074
	154.50	156.00	D022839	1.50	0.050		0.050
	156.00	157.50	D022841	1.50	<0.005		0.001
	157.50	159.00	D022842	1.50	<0.005		0.001
	159.00	160.50	D022843	1.50	<0.005		0.001
	160.50	162.00	D022844	1.50	0.019		0.019
	162.00	163.50	D022846	1.50	<0.005		0.001
	163.50	165.00	D022847	1.50	<0.005		0.001
	165.00	166.50	D022848	1.50	<0.005		0.001
	166.50	168.00	D022849	1.50	<0.005		0.001
	168.00	169.50	D022850	1.50	<0.005		0.001
	169.50	171.00	D022851	1.50	0.044		0.044
	171.00	172.50	D022852	1.50	0.105		0.105
	172.50	174.00	D022853	1.50	<0.005		0.001
	174.00	175.50	D022854	1.50	0.114		0.114
	175.50	177.00	D022856	1.50	0.128		0.128
	177.00	178.50	D022857	1.50	0.231		0.231
	178.50	180.00	D022858	1.50	0.006		0.006
	180.00	181.50	D022859	1.50	0.011		0.011
	181.50	183.00	D022860	1.50	<0.005		0.001
	183.00	184.50	D022861	1.50	0.845		0.845
	184.50	186.00	D022862	1.50	0.052		0.052
	186.00	187.50	D022863	1.50	0.023		0.023
	187.50	189.00	D022864	1.50	0.009		0.009
	189.00	190.50	D022866	1.50	0.010		0.010
	190.50	192.00	D022867	1.50	<0.005		0.001
	192.00	193.50	D022868	1.50	<0.005		0.001
	193.50	195.00	D022869	1.50	<0.005		0.001
	195.00	196.50	D022870	1.50	0.009		0.009
	196.50	198.00	D022871	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	198.00	199.50	D022872	1.50	<0.005		0.001
	199.50	201.00	D022873	1.50	<0.005		0.001
	201.00	202.50	D022874	1.50	<0.005		0.001
	202.50	204.00	D022876	1.50	<0.005		0.001
	204.00	205.50	D022877	1.50	<0.005		0.001
	205.50	207.00	D022878	1.50	0.055		0.055
	207.00	208.50	D022879	1.50	0.008		0.008
	208.50	210.00	D022881	1.50	0.031		0.031
	210.00	211.50	D022882	1.50	<0.005		0.001
	211.50	213.00	D022883	1.50	<0.005		0.001
	213.00	214.50	D022884	1.50	<0.005		0.001
	214.50	216.00	D022886	1.50	<0.005		0.001
	216.00	217.50	D022887	1.50	0.016		0.016
	217.50	219.00	D022888	1.50	<0.005		0.001
	219.00	220.50	D022889	1.50	<0.005		0.001
	220.50	222.00	D022890	1.50	<0.005		0.001
	222.00	223.50	D022891	1.50	<0.005		0.001
	223.50	225.00	D022892	1.50	<0.005		0.001
	225.00	226.40	D022893	1.40	0.035		0.035
	226.40	228.00	D022894	1.60	0.046		0.046
	228.00	229.50	D022896	1.50	<0.005		0.001
	229.50	231.00	D022897	1.50	<0.005		0.001
	231.00	232.50	D022898	1.50	<0.005		0.001
	232.50	234.00	D022899	1.50	<0.005		0.001
	234.00	235.50	D022900	1.50	<0.005		0.001
	235.50	237.00	D022901	1.50	<0.005		0.001
	237.00	238.50	D022902	1.50	<0.005		0.001
	238.50	240.00	D022903	1.50	<0.005		0.001
	240.00	241.50	D022904	1.50	<0.005		0.001
	241.50	243.00	D022906	1.50	<0.005		0.001
	243.00	244.50	D022907	1.50	<0.005		0.001
	244.50	246.00	D022908	1.50	<0.005		0.001
	246.00	247.50	D022909	1.50	0.005		0.005



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	247.50	249.00	D022910	1.50	<0.005		0.001
	249.00	250.50	D022911	1.50	<0.005		0.001
	250.50	252.00	D022912	1.50	<0.005		0.001
	252.00	253.50	D022913	1.50	<0.005		0.001
	253.50	255.00	D022914	1.50	<0.005		0.001
	255.00	256.50	D022916	1.50	<0.005		0.001
	256.50	258.00	D022917	1.50	0.006		0.006
	258.00	259.50	D022918	1.50	0.048		0.048
	259.50	261.00	D022919	1.50	0.021		0.021
	261.00	262.50	D022921	1.50	<0.005		0.001
	262.50	264.00	D022922	1.50	<0.005		0.001
	264.00	265.50	D022923	1.50	0.188		0.188
	265.50	267.00	D022924	1.50	0.008		0.008
	267.00	268.50	D022926	1.50	<0.005		0.001
	268.50	270.00	D022927	1.50	0.083		0.083
	270.00	271.50	D022928	1.50	0.006		0.006
	271.50	273.00	D022929	1.50	1.325		1.325
	273.00	274.50	D022930	1.50	0.077		0.077
	274.50	276.00	D022931	1.50	<0.005		0.001
	276.00	277.50	D022932	1.50	<0.005		0.001
	277.50	279.00	D022933	1.50	<0.005		0.001
	279.00	280.50	D022934	1.50	<0.005		0.001
	280.50	282.00	D022936	1.50	0.006		0.006
	282.00	283.50	D022937	1.50	0.026		0.026
	283.50	285.00	D022938	1.50	0.074		0.074
	285.00	286.50	D022939	1.50	1.170		1.170
	286.50	288.00	D022940	1.50	0.053		0.053
	288.00	289.50	D022941	1.50	<0.005		0.001
	289.50	291.00	D022942	1.50	0.007		0.007
	291.00	292.50	D022943	1.50	<0.005		0.001
	292.50	294.00	D022944	1.50	0.011		0.011
	294.00	295.50	D022946	1.50	0.101		0.101
	295.50	297.00	D022947	1.50	1.205		1.205

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	297.00	298.50	D022948	1.50	0.499		0.499
	298.50	300.00	D022949	1.50	0.094		0.094
	300.00	301.50	D022950	1.50	0.013		0.013
	301.50	303.00	D022951	1.50	0.015		0.015
	303.00	304.50	D022952	1.50	0.016		0.016
	304.50	306.00	D022953	1.50	0.109		0.109
	306.00	307.50	D022954	1.50	0.030		0.030
	307.50	309.00	D022956	1.50	0.008		0.008
	309.00	310.50	D022957	1.50	<0.005		0.001
	310.50	312.00	D022958	1.50	<0.005		0.001
	312.00	313.50	D022959	1.50	0.165		0.165
	313.50	315.00	D022961	1.50	0.010		0.010
	315.00	316.50	D022962	1.50	0.011		0.011
	316.50	318.00	D022963	1.50	0.023		0.023
	318.00	319.50	D022964	1.50	0.018		0.018
	319.50	321.00	D022966	1.50	0.036		0.036
	321.00	322.50	D022967	1.50	0.009		0.009
	322.50	324.00	D022968	1.50	0.009		0.009
	324.00	325.00	D022969	1.00	<0.005		0.001
	325.00	326.50	D022970	1.50	<0.005		0.001
	326.50	328.00	D022971	1.50	0.043		0.043
	328.00	329.50	D022972	1.50	0.221		0.221
	329.50	331.20	D022973	1.70	0.092		0.092
	331.20	332.90	D022974	1.70	<0.005		0.001
	332.90	334.50	D022976	1.60	<0.005		0.001
	334.50	336.00	D022977	1.50	<0.005		0.001
	336.00	337.50	D022978	1.50	0.338		0.338
	337.50	339.00	D022979	1.50	0.043		0.043
	339.00	340.00	D022980	1.00	<0.005		0.001
	340.00	341.70	D022981	1.70	0.200		0.200
	341.70	343.40	D022982	1.70	<0.005		0.001
	343.40	345.00	D022983	1.60	<0.005		0.001
	345.00	346.50	D022984	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	346.50	348.00	D022986	1.50	0.030		0.030
	348.00	349.50	D022987	1.50	0.051		0.051
	349.50	351.00	D022988	1.50	<0.005		0.001
	351.00	352.00	D022989	1.00	0.063		0.063
	352.00	353.50	D022990	1.50	0.128		0.128
	353.50	355.00	D022991	1.50	0.250		0.250
	355.00	356.50	D022992	1.50	0.006		0.006
	356.50	358.00	D022993	1.50	0.019		0.019
	358.00	359.50	D022994	1.50	0.032		0.032
	359.50	361.00	D022996	1.50	0.010		0.010
	361.00	362.50	D022997	1.50	<0.005		0.001
	362.50	364.00	D022998	1.50	0.141		0.141
	364.00	365.50	D022999	1.50	0.276		0.276
	365.50	366.50	D023001	1.00	0.047		0.047
	366.50	368.00	D023002	1.50	0.625		0.625
	368.00	369.00	D023003	1.00	0.366		0.366
	369.00	370.10	D023004	1.10	0.049		0.049
	370.10	371.80	D023006	1.70	2.510		2.510
	371.80	373.50	D023007	1.70	2.620		2.620
	373.50	375.00	D023008	1.50	0.120		0.120
	375.00	376.50	D023009	1.50	0.029		0.029
	376.50	378.00	D023010	1.50	0.184		0.184
	378.00	379.50	D023011	1.50	0.417		0.417
	379.50	381.00	D023012	1.50	0.008		0.008
	381.00	382.50	D023013	1.50	0.006		0.006
	382.50	384.00	D023014	1.50	0.132		0.132
	384.00	385.50	D023016	1.50	0.124		0.124
	385.50	387.00	D023017	1.50	0.156		0.156
	387.00	388.50	D023018	1.50	0.517		0.517
	388.50	390.00	D023019	1.50	0.177		0.177
	390.00	391.50	D023020	1.50	0.005		0.005
	391.50	393.00	D023021	1.50	0.005		0.005
	393.00	394.50	D023022	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	394.50	396.00	D023023	1.50	<0.005		0.001
	396.00	397.50	D023024	1.50	<0.005		0.001
	397.50	399.00	D023026	1.50	<0.005		0.001
	399.00	400.50	D023027	1.50	<0.005		0.001
	400.50	402.00	D023028	1.50	<0.005		0.001
	402.00	403.50	D023029	1.50	0.015		0.015
	403.50	405.00	D023030	1.50	<0.005		0.001
	405.00	406.50	D023031	1.50	0.234		0.234
	406.50	408.00	D023032	1.50	0.398		0.398
	408.00	409.50	D023033	1.50	0.010		0.010
	409.50	411.00	D023034	1.50	0.630		0.630
	411.00	412.50	D023036	1.50	0.037		0.037
	412.50	414.00	D023037	1.50	0.293		0.293
	414.00	415.50	D023038	1.50	0.604		0.604
	415.50	417.00	D023039	1.50	0.024		0.024
	417.00	418.50	D023041	1.50	0.186		0.186
	418.50	420.00	D023042	1.50	0.009		0.009
	420.00	421.50	D023043	1.50	<0.005		0.001
	421.50	423.00	D023044	1.50	<0.005		0.001
	423.00	424.50	D023045	1.50	0.230		0.230
	424.50	426.00	D023046	1.50	0.062		0.062
	426.00	427.50	D023048	1.50	0.874		0.874
	427.50	429.00	D023049	1.50	0.119		0.119
	429.00	430.50	D023050	1.50	0.071		0.071
	430.50	432.00	D023051	1.50	0.021		0.021
	432.00	433.50	D023052	1.50	0.048		0.048
	433.50	435.00	D023053	1.50	0.015		0.015
	435.00	436.50	D023054	1.50	0.091		0.091
	436.50	438.00	D023056	1.50	0.065		0.065
	438.00	439.50	D023057	1.50	0.490		0.490
	439.50	441.00	D023058	1.50	0.564		0.564
	441.00	442.50	D023059	1.50	0.606		0.606
	442.50	444.00	D023060	1.50	0.014		0.014

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	444.00	445.50	D023061	1.50	0.141		0.141
	445.50	447.00	D023062	1.50	0.011		0.011
	447.00	448.50	D023063	1.50	0.134		0.134
	448.50	450.00	D023064	1.50	0.194		0.194
	450.00	451.50	D023066	1.50	<0.005		0.001
	451.50	453.00	D023067	1.50	0.019		0.019
	453.00	454.50	D023068	1.50	0.051		0.051
	454.50	456.00	D023069	1.50	0.852		0.852
	456.00	457.50	D023070	1.50	0.436		0.436
	457.50	459.00	D023071	1.50	0.026		0.026
	459.00	460.50	D023072	1.50	0.256		0.256
	460.50	462.00	D023073	1.50	0.056		0.056
	462.00	463.50	D023074	1.50	0.022		0.022
	463.50	465.00	D023076	1.50	0.109		0.109
	465.00	466.20	D023077	1.20	0.025		0.025
	466.20	467.90	D023078	1.70	0.770		0.770
	467.90	469.50	D023079	1.60	0.151		0.151
	469.50	471.00	D023081	1.50	0.265		0.265
	471.00	472.50	D023082	1.50	0.769		0.769
	472.50	474.00	D023083	1.50	0.024		0.024
	474.00	475.50	D023084	1.50	0.028		0.028
	475.50	477.00	D023086	1.50	0.010		0.010
	477.00	478.50	D023087	1.50	0.022		0.022
	478.50	480.00	D023088	1.50	0.076		0.076
	480.00	481.50	D023089	1.50	0.008		0.008
	481.50	483.00	D023090	1.50	0.514		0.514
483.00	Fin du sondage Nombre d'échantillons : 322 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 480.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
17.50	17.50	D022735	L	0.00	2.310	2.310
31.00	32.50	D022745	D022744	1.50	0.034	0.034
44.00	45.50	D022755	M	1.50	3.070	3.070
50.00	50.00	D022760	M1	0.00	<0.005	0.001
56.00	57.50	D022765	D022764	1.50	0.023	0.023
69.50	69.50	D022775	J	0.00	0.796	0.796
83.00	84.50	D022785	D022784	1.50	0.124	0.124
96.50	96.50	D022795	K	0.00	1.080	1.080
102.50	102.50	D022800	M1	0.00	<0.005	0.001
108.50	110.00	D022805	D022804	1.50	<0.005	0.001
122.00	122.00	D022815	J	0.00	0.747	0.747
135.50	137.00	D022825	D022824	1.50	<0.005	0.001
148.50	148.50	D022835	K	0.00	1.075	1.075
154.50	154.50	D022840	M1	0.00	<0.005	0.001
160.50	162.00	D022845	D022844	1.50	0.010	0.010
174.00	174.00	D022855	L	0.00	2.450	2.450
187.50	189.00	D022865	D022864	1.50	0.009	0.009
201.00	201.00	D022875	M	0.00	3.080	3.080
207.00	207.00	D022880	M1	0.00	<0.005	0.001
213.00	214.50	D022885	D022884	1.50	<0.005	0.001
226.50	226.50	D022895	J	0.00	0.747	0.747
240.00	241.50	D022905	D022904	1.50	<0.005	0.001
253.50	255.00	D022915	K	1.50	0.904	0.904
259.50	259.50	D022920	M1	0.00	<0.005	0.001
265.50	267.00	D022925	D022924	1.50	0.007	0.007
279.00	279.00	D022935	J	0.00	0.755	0.755
292.50	294.00	D022945	D022944	1.50	0.013	0.013
306.00	306.00	D022955	K	0.00	1.025	1.025
312.00	312.00	D022960	M1	0.00	<0.005	0.001
318.00	319.50	D022965	D022964	1.50	0.021	0.021
331.20	331.20	D022975	L	0.00	2.250	2.250
345.00	346.50	D022985	D022984	1.50	<0.005	0.001
358.00	358.00	D022995	M	0.00	3.130	3.130

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
364.00	364.00	D023000	M1	0.00	<0.005	0.001
369.00	370.10	D023005	D023004	1.10	0.057	0.057
382.50	382.50	D023015	J	0.00	0.801	0.801
396.00	397.50	D023025	D023024	1.50	<0.005	0.001
409.50	409.50	D023035	K	0.00	0.997	0.997
415.50	417.00	D023040	D023039	1.50	0.030	0.030
424.50	424.50	D023047	M1	0.00	<0.005	0.001
435.00	435.00	D023055	J	0.00	0.794	0.794
448.50	450.00	D023065	D023064	1.50	0.213	0.213
462.00	462.00	D023075	K	0.00	1.150	1.150
467.90	467.90	D023080	M1	0.00	<0.005	0.001
474.00	475.50	D023085	D023084	1.50	0.033	0.033

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-224</b>	Titre minier :	Section :	630700
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : Gilles.KAMTA	Du : 2010-07-23	Date de description :	2010-07-14
	Au : 2010-06-27		

Collet

Azimut : 180.00°  
 Plongée : -60.00°  
 Longueur : 286.00 m

UTM

Est	630 700.0
Nord	5 374 250.6
Élévation	314.0

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	1.00	0.00°	0.00°	Oui
Reflex	4.00	185.30°	-59.50°	Non
Reflex	7.00	185.70°	-60.00°	Non
Reflex	10.00	197.60°	-72.60°	Oui
Reflex	13.00	184.00°	-59.80°	Non
Reflex	16.00	183.70°	-59.20°	Non
Reflex	19.00	184.40°	-59.90°	Non
Reflex	22.00	185.90°	-60.20°	Non
Reflex	25.00	184.30°	-59.80°	Non
Reflex	28.00	183.80°	-59.80°	Non
Reflex	31.00	178.60°	-58.40°	Oui
Reflex	34.00	184.20°	-59.90°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	37.00	184.10°	-59.80°	Non
Reflex	40.00	184.50°	-59.70°	Non
Reflex	43.00	185.10°	-59.90°	Non
Reflex	46.00	183.80°	-59.70°	Non
Reflex	49.00	184.20°	-60.00°	Non
Reflex	52.00	184.40°	-60.30°	Non
Reflex	55.00	182.60°	-61.80°	Non
Reflex	58.00	182.20°	-60.70°	Non
Reflex	61.00	186.10°	-60.10°	Oui
Reflex	64.00	185.50°	-60.10°	Non
Reflex	67.00	219.30°	-48.50°	Oui
Reflex	70.00	184.90°	-60.20°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	73.00	182.40°	-62.40°	Oui	Reflex	172.00	188.70°	-60.10°	Non
Reflex	76.00	186.20°	-58.70°	Non	Reflex	175.00	186.50°	-60.00°	Non
Reflex	79.00	185.10°	-60.50°	Non	Reflex	178.00	186.00°	-59.80°	Non
Reflex	82.00	185.40°	-60.20°	Non	Reflex	181.00	185.80°	-59.70°	Non
Reflex	85.00	185.80°	-60.30°	Non	Reflex	184.00	187.50°	-59.60°	Non
Reflex	88.00	185.30°	-60.50°	Non	Reflex	187.00	185.60°	-59.50°	Non
Reflex	91.00	184.90°	-61.00°	Non	Reflex	190.00	186.20°	-59.50°	Non
Reflex	94.00	188.60°	-57.80°	Oui	Reflex	193.00	185.70°	-59.50°	Non
Reflex	97.00	186.50°	-60.30°	Non	Reflex	196.00	185.40°	-59.50°	Non
Reflex	100.00	185.50°	-60.70°	Non	Reflex	199.00	185.50°	-59.50°	Non
Reflex	103.00	185.80°	-60.60°	Non	Reflex	202.00	186.60°	-59.50°	Non
Reflex	106.00	185.80°	-60.50°	Non	Reflex	205.00	187.00°	-59.40°	Non
Reflex	109.00	185.80°	-60.60°	Non	Reflex	208.00	186.90°	-59.50°	Non
Reflex	112.00	186.20°	-60.60°	Non	Reflex	211.00	185.00°	-59.50°	Non
Reflex	115.00	186.20°	-60.60°	Non	Reflex	214.00	186.00°	-59.20°	Non
Reflex	118.00	187.10°	-60.90°	Non	Reflex	217.00	186.40°	-59.50°	Non
Reflex	121.00	187.10°	-60.70°	Non	Reflex	220.00	187.30°	-59.40°	Non
Reflex	124.00	186.70°	-60.60°	Non	Reflex	223.00	187.50°	-59.40°	Non
Reflex	127.00	186.30°	-60.70°	Non	Reflex	226.00	187.30°	-59.60°	Non
Reflex	130.00	185.70°	-60.60°	Non	Reflex	229.00	188.60°	-58.90°	Non
Reflex	133.00	186.00°	-60.60°	Non	Reflex	232.00	188.10°	-59.40°	Non
Reflex	136.00	186.10°	-60.60°	Non	Reflex	235.00	188.10°	-59.40°	Non
Reflex	139.00	186.50°	-60.70°	Non	Reflex	238.00	188.50°	-59.40°	Non
Reflex	142.00	185.30°	-60.60°	Non	Reflex	241.00	188.60°	-59.40°	Non
Reflex	145.00	186.10°	-60.50°	Non	Reflex	244.00	189.00°	-59.40°	Non
Reflex	148.00	185.50°	-60.60°	Non	Reflex	247.00	189.20°	-59.30°	Non
Reflex	151.00	186.10°	-60.70°	Non	Reflex	250.00	189.70°	-59.30°	Non
Reflex	154.00	185.90°	-60.50°	Non	Reflex	253.00	189.80°	-59.10°	Non
Reflex	157.00	185.90°	-60.50°	Non	Reflex	256.00	190.10°	-59.00°	Non
Reflex	160.00	185.60°	-60.50°	Non	Reflex	259.00	190.20°	-58.90°	Non
Reflex	163.00	186.40°	-60.50°	Non	Reflex	262.00	190.20°	-58.90°	Non
Reflex	166.00	194.10°	-58.80°	Oui	Reflex	265.00	190.10°	-58.80°	Non
Reflex	169.00	187.60°	-60.30°	Non	Reflex	268.00	190.20°	-58.70°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	271.00	190.20°	-58.60°	Non					
Reflex	274.00	190.30°	-58.60°	Non					
Reflex	277.00	189.90°	-58.50°	Non					
Reflex	280.00	190.50°	-58.50°	Non					
Reflex	283.00	190.40°	-58.40°	Non					
Reflex	286.00	190.40°	-58.40°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.90	MT						
		<b>Mort-terrain</b>						
1.90	155.90	SY; MAS; FIN; MTY	1.90	3.50	D028919	1.60	<0.005	0.001
		<b>Syénite; Roche massive; Grains fins; Grains moyens</b>	3.50	5.00	D028920	1.50	<0.005	0.001
		grenue, quelques phénocristaux de FP irrég diss, localement altéré en calcite, fortement hématisé, oxydes de carbonâtes, séricite, chlorite	5.00	6.50	D028921	1.50	<0.005	0.001
			6.50	8.00	D028922	1.50	<0.005	0.001
			8.00	9.50	D028923	1.50	<0.005	0.001
			9.50	11.00	D028924	1.50	<0.005	0.001
			11.00	12.50	D028925	1.50	<0.005	0.001
			12.50	14.00	D028926	1.50	<0.005	0.001
			14.00	15.50	D028927	1.50	<0.005	0.001
			15.50	17.00	D028929	1.50	<0.005	0.001
			17.00	18.50	D028930	1.50	0.055	0.055
17.90	18.40	FRC	18.50	20.00	D028931	1.50	0.010	0.010
		<b>Fracturé 50°</b>	20.00	21.50	D028932	1.50	0.005	0.005
		fragments cm	21.50	23.00	D028933	1.50	0.048	0.048
			23.00	24.50	D028934	1.50	0.194	0.194
			24.50	26.00	D028935	1.50	0.026	0.026
			26.00	27.50	D028936	1.50	0.056	0.056
			27.50	29.00	D028937	1.50	0.061	0.061
			29.00	30.50	D028939	1.50	0.207	0.207
			30.50	32.00	D028940	1.50	0.084	0.084
			32.00	33.50	D028941	1.50	0.153	0.153
			33.50	35.00	D028942	1.50	<0.005	0.001
			35.00	36.50	D028943	1.50	0.062	0.062
			36.50	38.00	D028944	1.50	0.013	0.013
			38.00	39.50	D028945	1.50	0.972	0.972
			39.50	41.00	D028946	1.50	0.204	0.204
			41.00	42.50	D028947	1.50	0.277	0.277
			42.50	44.00	D028949	1.50	0.099	0.099
			44.00	45.50	D028950	1.50	0.096	0.096
			45.50	47.00	D028951	1.50	0.328	0.328
			47.00	48.50	D028952	1.50	0.337	0.337

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.50	50.00	D028953	1.50	0.173		0.173
	50.00	51.50	D028954	1.50	0.084		0.084
	51.50	53.00	D028956	1.50	0.442		0.442
	53.00	54.50	D028957	1.50	1.600		1.600
	54.50	56.00	D028959	1.50	0.080		0.080
	56.00	57.50	D028960	1.50	<0.005		0.001
	57.50	59.00	D028961	1.50	0.005		0.005
	59.00	60.50	D028962	1.50	0.006		0.006
	60.50	62.00	D028963	1.50	<0.005		0.001
	62.00	63.50	D028964	1.50	<0.005		0.001
	63.50	65.00	D028965	1.50	<0.005		0.001
	65.00	66.50	D028966	1.50	<0.005		0.001
	66.50	68.00	D028967	1.50	0.145		0.145
	68.00	69.50	D028969	1.50	<0.005		0.001
	69.50	71.00	D028970	1.50	0.022		0.022
	71.00	72.50	D028971	1.50	0.010		0.010
	72.50	74.00	D028972	1.50	0.007		0.007
	74.00	75.50	D028973	1.50	0.009		0.009
	75.50	77.00	D028974	1.50	0.015		0.015
	77.00	78.50	D028975	1.50	0.016		0.016
	78.50	80.00	D028976	1.50	0.919		0.919
	80.00	81.50	D028977	1.50	0.843		0.843
	81.50	83.00	D028979	1.50	0.450		0.450
	83.00	84.50	D028980	1.50	0.381		0.381
	84.50	86.00	D028981	1.50	0.131		0.131
	86.00	87.50	D028982	1.50	0.335		0.335
	87.50	89.00	D028983	1.50	0.203		0.203
	89.00	90.50	D028984	1.50	1.205		1.205
	90.50	92.00	D028985	1.50	2.920		2.920
	92.00	93.50	D028986	1.50	1.840		1.840
	93.50	95.00	D028987	1.50	1.930		1.930
	95.00	96.50	D028989	1.50	1.875		1.875
	96.50	98.00	D028990	1.50	4.050		4.050

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
126.00      140.00 SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP 0.2-0.7 cm automorphe ou sub arrondi	98.00	99.00	D028991	1.00	5.240		5.240
	99.00	100.00	D028992	1.00	1.805		1.805
	100.00	101.00	D028993	1.00	3.070		3.070
	101.00	102.50	D028994	1.50	1.995		1.995
	102.50	104.00	D028996	1.50	0.685		0.685
	104.00	105.50	D028997	1.50	0.463		0.463
	105.50	107.00	D028999	1.50	0.991		0.991
	107.00	108.50	D029000	1.50	0.482		0.482
	108.50	110.00	D029001	1.50	0.467		0.467
	110.00	111.50	D029002	1.50	0.229		0.229
	111.50	113.00	D029003	1.50	0.197		0.197
	113.00	114.50	D029004	1.50	0.500		0.500
	114.50	116.00	D029005	1.50	0.172		0.172
	116.00	117.50	D029006	1.50	0.103		0.103
	117.50	119.00	D029007	1.50	0.106		0.106
	119.00	120.50	D029009	1.50	0.387		0.387
	120.50	122.00	D029010	1.50	0.902		0.902
	122.00	123.50	D029011	1.50	0.383		0.383
	123.50	125.00	D029012	1.50	0.449		0.449
	125.00	126.50	D029013	1.50	0.789		0.789
	126.50	128.00	D029014	1.50	0.110		0.110
	128.00	129.50	D029015	1.50	0.267		0.267
	129.50	131.00	D029016	1.50	0.310		0.310
	131.00	132.50	D029017	1.50	0.498		0.498
	132.50	134.00	D029019	1.50	0.317		0.317
	134.00	135.50	D029020	1.50	0.393		0.393
	135.50	137.00	D029021	1.50	1.120		1.120
137.00	138.50	D029022	1.50	0.340		0.340	
138.50	140.00	D029023	1.50	0.171		0.171	
140.00	141.50	D029024	1.50	0.341		0.341	
141.50	143.00	D029025	1.50	0.688		0.688	
143.00	144.50	D029026	1.50	0.531		0.531	
144.50	146.00	D029027	1.50	0.091		0.091	

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			146.00	147.50	D029029	1.50		0.012		0.012
			147.50	149.00	D029030	1.50		0.107		0.107
			149.00	150.50	D029031	1.50		0.024		0.024
			150.50	152.00	D029032	1.50		0.016		0.016
			152.00	153.50	D029033	1.50		<0.005		0.001
153.50	155.00	SY; POR	153.50	154.70	D029034	1.20		0.037		0.037
		<b>Syénite; Porphyrique</b>	154.70	155.90	D029036	1.20		0.093		0.093
		phénocristaux de FP 0.2-0.6 cm								
155.90	170.90	BA; MAS; AMY	155.90	157.50	D029037	1.60		0.686		0.686
		<b>Basalte 50°; Roche massive; Amygdalaire</b>	157.50	159.00	D029039	1.50		1.540		1.540
		massive localement bréchifié ou cisailé, hématisation, chloritisation, carbonâtes, PY fine irrég diss	159.00	160.50	D029040	1.50		3.600		3.600
			160.50	162.00	D029041	1.50		0.350		0.350
			162.00	163.50	D029042	1.50		2.990		2.990
			163.50	165.00	D029043	1.50		0.130		0.130
			165.00	166.50	D029044	1.50		0.020		0.020
			166.50	168.00	D029045	1.50		<0.005		0.001
			168.00	169.50	D029046	1.50		0.006		0.006
			169.50	170.90	D029047	1.40		0.007		0.007
155.90	163.50	BA; BRC; AMY								
		<b>Basalte 50°; Brèche de coulée; Amygdalaire</b>								
		basalte remplacé, fragments sub automorphe ou arrondi, légèrement blanchi, séricitisé, chloritisé et hématisé, PY fine diss								
170.90	182.70	GA; FIN	170.90	172.50	D029049	1.60		<0.005		0.001
		<b>Gabbro 50°; Grains fins</b>	172.50	174.00	D029050	1.50		<0.005		0.001
		grenue, altéré en séricite et chlorite, leucoxènes, veinules et veines carbonaté, PY irrég diss	174.00	175.50	D029051	1.50		<0.005		0.001
			175.50	177.00	D029052	1.50		<0.005		0.001
			177.00	178.50	D029053	1.50		<0.005		0.001
			178.50	180.00	D029054	1.50		<0.005		0.001
			180.00	181.50	D029055	1.50		<0.005		0.001
			181.50	182.70	D029056	1.20		<0.005		0.001
182.70	209.20	SY; FIN	182.70	184.00	D029057	1.30		0.063		0.063
		<b>Syénite 60°; Grains fins</b>	184.00	185.50	D029059	1.50		<0.005		0.001
		grenue, localement qlq phénocristaux de FP sub arrondi, hématisation légère chloritisation et séricitisation, carbonâtes	185.50	187.00	D029060	1.50		<0.005		0.001
			187.00	188.50	D029061	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			188.50	190.00	D029062	1.50	<0.005		0.001
			190.00	191.50	D029063	1.50	<0.005		0.001
			191.50	193.00	D029064	1.50	<0.005		0.001
			193.00	194.50	D029065	1.50	<0.005		0.001
			194.50	196.00	D029066	1.50	<0.005		0.001
			196.00	197.50	D029067	1.50	<0.005		0.001
			197.50	199.00	D029069	1.50	<0.005		0.001
			199.00	200.50	D029070	1.50	<0.005		0.001
			200.50	202.00	D029071	1.50	<0.005		0.001
			202.00	203.50	D029072	1.50	<0.005		0.001
			203.50	205.00	D029073	1.50	<0.005		0.001
			205.00	206.50	D029074	1.50	<0.005		0.001
			206.50	208.00	D029076	1.50	<0.005		0.001
			208.00	209.20	D029077	1.20	<0.005		0.001
209.20	215.40	GA; FIN	209.20	210.50	D029079	1.30	0.104		0.104
		<b>Gabbro 60°; Grains fins</b>	210.50	212.00	D029080	1.50	<0.005		0.001
		grenue, altération en chlorite, carbonates, SR+, oxydes de carbonates, PY fine	212.00	213.40	D029081	1.40	<0.005		0.001
			213.40	214.40	D029082	1.00	<0.005		0.001
			214.40	215.40	D029083	1.00	<0.005		0.001
215.40	233.00	SY; FIN	215.40	217.00	D029084	1.60	0.005		0.005
		<b>Syénite 60°; Grains fins</b>	217.00	218.50	D029085	1.50	0.779		0.779
		phénocristaux de FP automorphe zoné 0.2-1 cm, localement altéré en silice aspect cherteux, brêchifications, oxydes de carbonates, SR+, CL++, HM+, PY fine diss	218.50	220.00	D029086	1.50	0.050		0.050
			220.00	221.50	D029087	1.50	0.008		0.008
			221.50	223.00	D029089	1.50	0.021		0.021
			223.00	224.50	D029090	1.50	0.015		0.015
			224.50	226.00	D029091	1.50	0.025		0.025
			226.00	227.50	D029092	1.50	0.016		0.016
			227.50	229.00	D029093	1.50	0.017		0.017
			229.00	230.50	D029094	1.50	0.011		0.011
			230.50	232.00	D029095	1.50	0.007		0.007
			232.00	233.00	D029096	1.00	0.018		0.018
233.00	246.50	CG; FIN	233.00	234.50	D029097	1.50	0.013		0.013
		<b>Conglomérat 50°; Grains fins</b>	234.50	236.00	D029099	1.50	0.023		0.023
		grenue, grès fin avec fragments anguleux 0.1-3 cm brêchifiant la							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
246.50	270.00	roche, BO++, HM+, localement phénocristaux de FP ou carbonâtes PY irrég diss  GR; FIN; MAS <b>Grès; Grains fins; Roche massive</b> grenue, grains equigranulaire, localement passage de mudstone, litage, lamination, légère chloritisation, graphite, calcite biotite	236.00	237.50	D029100	1.50	0.019		0.019
			237.50	239.00	D029101	1.50	0.006		0.006
			239.00	240.50	D029102	1.50	<0.005		0.001
			240.50	242.00	D029103	1.50	0.013		0.013
			242.00	243.50	D029104	1.50	0.015		0.015
			243.50	245.00	D029105	1.50	0.014		0.014
			245.00	246.50	D029106	1.50	0.024		0.024
			246.50	248.00	D029107	1.50	0.017		0.017
			248.00	249.50	D029109	1.50	0.008		0.008
			249.50	251.00	D029110	1.50	0.024		0.024
			251.00	252.50	D029111	1.50	0.020		0.020
			252.50	254.00	D029112	1.50	0.013		0.013
			254.00	255.50	D029113	1.50	0.011		0.011
			255.50	257.00	D029114	1.50	0.021		0.021
			257.00	258.50	D029116	1.50	0.020		0.020
			258.50	260.00	D029117	1.50	0.007		0.007
			270.00	286.00	UM; RUB <b>Ultramafite serpentinisée 40°; Rubané</b> aphanitique, carbonaté, talc, légèrement chloritisé, altération en calcite, PY irrég diss	260.00	261.50	D029119	1.50
261.50	263.00	D029120				1.50	0.013		0.013
263.00	264.50	D029121				1.50	0.013		0.013
264.50	266.00	D029122				1.50	0.006		0.006
266.00	267.50	D029123				1.50	0.287		0.287
267.50	269.00	D029124				1.50	<0.005		0.001
269.00	270.00	D029125				1.00	0.010		0.010
270.00	271.50	D029126				1.50	0.550		0.550
271.50	273.00	D029127				1.50	0.006		0.006
273.00	274.50	D029129				1.50	<0.005		0.001
274.50	276.00	D029130				1.50	0.008		0.008
276.00	277.50	D029131				1.50	<0.005		0.001
277.50	279.00	D029132				1.50	0.007		0.007
279.00	280.50	D029133				1.50	<0.005		0.001
280.50	282.00	D029134				1.50	<0.005		0.001
282.00	283.50	D029135				1.50	<0.005		0.001
283.50	285.00	D029136				1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	285.00	286.00	D029137	1.00	<0.005		0.001
286.00 Fin du sondage Nombre d'échantillons : 193 Nombre d'échantillons QAQC : 27 Longueur totale échantillonnée : 284.10							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	15.50	D028928	D028927	1.50	<0.005	0.001
27.50	27.50	D028938	J	0.00	0.681	0.681
41.00	42.50	D028948	D028947	1.50	0.250	0.250
50.00	50.00	D028955	M1	0.00	<0.005	0.001
53.00	53.00	D028958	K	0.00	1.180	1.180
66.50	68.00	D028968	D028967	1.50	0.070	0.070
80.00	80.00	D028978	L	0.00	2.320	2.320
93.50	95.00	D028988	D028987	1.50	1.825	1.825
101.00	101.00	D028995	M1	0.00	0.011	0.011
104.00	104.00	D028998	M	0.00	3.220	3.220
117.50	119.00	D029008	D029007	1.50	0.094	0.094
131.00	131.00	D029018	J	0.00	0.830	0.830
144.50	146.00	D029028	D029027	1.50	0.055	0.055
153.50	153.50	D029035	M1	0.00	<0.005	0.001
155.90	155.90	D029038	K	0.00	1.050	1.050
169.50	170.90	D029048	D029047	1.40	0.007	0.007
182.70	182.70	D029058	J	0.00	0.812	0.812
196.00	197.50	D029068	D029067	1.50	<0.005	0.001
205.00	205.00	D029075	M1	0.00	<0.005	0.001
209.20	209.20	D029078	M	0.00	3.230	3.230
220.00	221.50	D029088	D029087	1.50	0.008	0.008
233.00	233.00	D029098	J	0.00	0.792	0.792
246.50	248.00	D029108	D029107	1.50	0.018	0.018
255.50	255.50	D029115	M1	0.00	<0.005	0.001
258.50	258.50	D029118	K	0.00	1.045	1.045
271.50	273.00	D029128	D029127	1.50	0.008	0.008
285.00	285.00	D029138	L	0.00	2.310	2.310



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	358.60°	-60.30°	Non	Reflex	173.00	2.80°	-60.80°	Non
Reflex	77.00	358.80°	-60.30°	Non	Reflex	176.00	3.00°	-60.80°	Non
Reflex	80.00	359.30°	-60.30°	Non	Reflex	179.00	3.00°	-60.80°	Non
Reflex	83.00	358.20°	-60.40°	Non	Reflex	182.00	2.70°	-60.70°	Non
Reflex	86.00	359.60°	-60.40°	Non	Reflex	185.00	2.70°	-60.70°	Non
Reflex	89.00	0.00°	-60.40°	Non	Reflex	188.00	3.10°	-60.80°	Non
Reflex	92.00	359.30°	-60.40°	Non	Reflex	191.00	3.60°	-60.80°	Non
Reflex	95.00	359.50°	-60.40°	Non	Reflex	194.00	1.80°	-60.70°	Oui
Reflex	98.00	1.30°	-60.50°	Oui	Reflex	197.00	3.30°	-60.80°	Non
Reflex	101.00	359.50°	-60.50°	Non	Reflex	200.00	5.00°	-60.80°	Oui
Reflex	104.00	0.80°	-60.50°	Non	Reflex	203.00	4.10°	-60.80°	Non
Reflex	107.00	0.20°	-60.40°	Non	Reflex	206.00	3.50°	-60.80°	Non
Reflex	110.00	359.80°	-60.60°	Non	Reflex	209.00	3.30°	-60.70°	Non
Reflex	113.00	0.50°	-60.50°	Non	Reflex	212.00	4.50°	-60.80°	Non
Reflex	116.00	0.40°	-60.50°	Non	Reflex	215.00	4.70°	-60.80°	Non
Reflex	119.00	1.90°	-60.60°	Non	Reflex	218.00	6.00°	-60.80°	Non
Reflex	122.00	1.50°	-60.60°	Non	Reflex	221.00	5.40°	-60.90°	Non
Reflex	125.00	1.30°	-60.60°	Non	Reflex	224.00	5.60°	-60.90°	Non
Reflex	128.00	1.20°	-60.60°	Non	Reflex	227.00	4.70°	-60.90°	Non
Reflex	131.00	2.00°	-60.60°	Non	Reflex	230.00	6.30°	-60.90°	Non
Reflex	134.00	2.60°	-60.70°	Non	Reflex	233.00	6.10°	-60.90°	Non
Reflex	137.00	0.50°	-60.60°	Oui	Reflex	236.00	6.20°	-60.90°	Non
Reflex	140.00	0.00°	-60.50°	Oui	Reflex	239.00	6.00°	-60.90°	Non
Reflex	143.00	1.20°	-60.60°	Non	Reflex	242.00	6.00°	-60.90°	Non
Reflex	146.00	1.50°	-60.50°	Non	Reflex	245.00	5.50°	-60.90°	Non
Reflex	149.00	1.30°	-60.60°	Non	Reflex	248.00	5.60°	-60.90°	Non
Reflex	152.00	0.80°	-60.60°	Non	Reflex	251.00	7.00°	-60.90°	Non
Reflex	155.00	1.30°	-60.70°	Non	Reflex	254.00	4.50°	-60.90°	Oui
Reflex	158.00	1.20°	-60.70°	Non	Reflex	257.00	6.90°	-60.90°	Non
Reflex	161.00	2.40°	-60.70°	Non	Reflex	260.00	7.40°	-60.90°	Non
Reflex	164.00	2.40°	-60.70°	Non	Reflex	263.00	7.00°	-60.80°	Non
Reflex	167.00	2.50°	-60.80°	Non	Reflex	266.00	7.70°	-60.90°	Non
Reflex	170.00	2.60°	-60.80°	Non	Reflex	269.00	7.20°	-60.90°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	7.80°	-60.90°	Non	Reflex	371.00	5.90°	-60.20°	Non
Reflex	275.00	7.20°	-60.90°	Non	Reflex	374.00	6.00°	-60.20°	Non
Reflex	278.00	7.80°	-60.90°	Non	Reflex	377.00	6.90°	-60.20°	Non
Reflex	281.00	6.80°	-60.90°	Non	Reflex	380.00	6.70°	-60.20°	Non
Reflex	284.00	6.90°	-60.80°	Non	Reflex	383.00	4.60°	-60.20°	Non
Reflex	287.00	6.30°	-60.80°	Non	Reflex	386.00	4.10°	-60.20°	Non
Reflex	290.00	7.30°	-60.70°	Non	Reflex	389.00	4.80°	-60.20°	Non
Reflex	293.00	7.20°	-60.70°	Non	Reflex	392.00	4.80°	-60.20°	Non
Reflex	296.00	7.00°	-60.70°	Non	Reflex	395.00	5.00°	-60.10°	Non
Reflex	299.00	6.70°	-60.70°	Non	Reflex	398.00	4.40°	-60.20°	Non
Reflex	302.00	6.30°	-60.60°	Non	Reflex	401.00	6.50°	-60.20°	Oui
Reflex	305.00	6.50°	-60.50°	Non	Reflex	404.00	5.70°	-60.20°	Non
Reflex	308.00	5.30°	-60.40°	Oui	Reflex	407.00	5.70°	-60.20°	Non
Reflex	311.00	6.80°	-60.40°	Non	Reflex	410.00	5.70°	-60.10°	Non
Reflex	314.00	5.90°	-60.50°	Oui	Reflex	413.00	6.10°	-60.20°	Non
Reflex	317.00	7.10°	-60.50°	Non	Reflex	416.00	6.40°	-60.20°	Non
Reflex	320.00	10.10°	-60.50°	Non	Reflex	419.00	7.00°	-60.10°	Non
Reflex	323.00	5.80°	-60.50°	Non	Reflex	422.00	7.20°	-60.10°	Non
Reflex	326.00	5.80°	-60.50°	Non	Reflex	425.00	7.30°	-60.10°	Non
Reflex	329.00	6.70°	-60.50°	Non	Reflex	428.00	7.40°	-60.00°	Non
Reflex	332.00	6.60°	-60.50°	Non	Reflex	431.00	7.90°	-60.00°	Non
Reflex	335.00	4.80°	-60.40°	Non	Reflex	434.00	5.80°	-59.90°	Oui
Reflex	338.00	5.30°	-60.40°	Non	Reflex	437.00	7.80°	-59.80°	Non
Reflex	341.00	5.60°	-60.40°	Non	Reflex	440.00	5.80°	-59.80°	Oui
Reflex	344.00	5.70°	-60.40°	Non	Reflex	443.00	7.20°	-59.80°	Non
Reflex	347.00	5.70°	-60.30°	Non	Reflex	446.00	7.70°	-59.70°	Non
Reflex	350.00	5.80°	-60.30°	Non	Reflex	449.00	9.20°	-59.60°	Non
Reflex	353.00	6.00°	-60.30°	Non	Reflex	452.00	8.40°	-59.50°	Non
Reflex	356.00	6.20°	-60.30°	Non	Reflex	455.00	7.60°	-59.50°	Non
Reflex	359.00	6.50°	-60.30°	Non	Reflex	458.00	9.30°	-59.40°	Non
Reflex	362.00	6.90°	-60.20°	Non	Reflex	461.00	9.40°	-59.50°	Non
Reflex	365.00	5.60°	-60.30°	Non	Reflex	464.00	8.90°	-59.40°	Non
Reflex	368.00	5.90°	-60.30°	Non	Reflex	467.00	8.80°	-59.40°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	9.20°	-59.30°	Non					
Reflex	473.00	9.30°	-59.20°	Non					
Reflex	476.00	9.40°	-59.10°	Non					
Reflex	479.00	9.60°	-59.00°	Non					
Reflex	482.00	9.70°	-58.90°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	1.30	MT						
		<b>Mort-terrain</b>						
1.30	482.00	SY; FIN; MTY	1.30	3.00	D019856	1.70	<0.005	0.001
		<b>Syénite; Grains fins; Grains moyens</b>						
		Microgrenu, équi-granulaire, grains fins à grains moyens, avec passage de quelques phénocristaux de feldasph Xmm.						
			3.00	4.50	D019858	1.50	<0.005	0.001
			4.50	6.00	D019859	1.50	0.037	0.037
			6.00	7.50	D019860	1.50	<0.005	0.001
			7.50	9.00	D019861	1.50	<0.005	0.001
			9.00	10.50	D019863	1.50	<0.005	0.001
			10.50	12.00	D019864	1.50	0.343	0.343
			12.00	13.50	D019865	1.50	0.047	0.047
			13.50	15.00	D019866	1.50	0.012	0.012
			15.00	16.50	D019868	1.50	0.012	0.012
			16.50	18.00	D019869	1.50	<0.005	0.001
			18.00	19.50	D019870	1.50	<0.005	0.001
			19.50	21.00	D019871	1.50	0.009	0.009
			21.00	22.50	D019872	1.50	1.115	1.115
			22.50	24.00	D019873	1.50	0.112	0.112
			24.00	25.50	D019874	1.50	0.478	0.478
			25.50	27.00	D019875	1.50	<0.005	0.001
			27.00	28.50	D019876	1.50	0.005	0.005
			28.50	30.00	D019878	1.50	0.005	0.005
			30.00	31.50	D019879	1.50	0.011	0.011
			31.50	33.00	D019880	1.50	0.054	0.054
			33.00	34.50	D019881	1.50	0.273	0.273
			34.50	36.00	D019882	1.50	0.301	0.301
			36.00	37.50	D019883	1.50	0.160	0.160
			37.50	39.00	D019884	1.50	0.008	0.008
			39.00	40.50	D019885	1.50	0.133	0.133
			40.50	42.00	D019886	1.50	<0.005	0.001
			42.00	43.50	D019888	1.50	0.010	0.010
			43.50	45.00	D019889	1.50	0.058	0.058
			45.00	46.50	D019890	1.50	0.936	0.936
			46.50	48.00	D019891	1.50	0.398	0.398
			48.00	49.50	D019892	1.50	0.053	0.053

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	49.50	51.00	D019893	1.50	0.017		0.017
	51.00	52.50	D019894	1.50	<0.005		0.001
	52.50	54.00	D019895	1.50	<0.005		0.001
	54.00	55.50	D019896	1.50	<0.005		0.001
	55.50	57.00	D019898	1.50	0.122		0.122
	57.00	58.50	D019899	1.50	0.721		0.721
	58.50	60.00	D019900	1.50	0.104		0.104
	60.00	61.50	D019901	1.50	0.074		0.074
	61.50	63.00	D019903	1.50	0.117		0.117
	63.00	64.50	D019904	1.50	0.085		0.085
	64.50	66.00	D019905	1.50	0.110		0.110
	66.00	67.50	D019906	1.50	<0.005		0.001
	67.50	69.00	D019908	1.50	0.014		0.014
	69.00	70.50	D019909	1.50	0.026		0.026
	70.50	72.00	D019910	1.50	0.008		0.008
	72.00	73.50	D019911	1.50	0.031		0.031
	73.50	75.00	D019912	1.50	0.008		0.008
	75.00	76.50	D019913	1.50	0.013		0.013
	76.50	78.00	D019914	1.50	0.014		0.014
	78.00	79.50	D019915	1.50	<0.005		0.001
	79.50	81.00	D019916	1.50	<0.005		0.001
	81.00	82.50	D019918	1.50	0.011		0.011
	82.50	84.00	D019919	1.50	<0.005		0.001
	84.00	85.50	D019920	1.50	<0.005		0.001
	85.50	87.00	D019921	1.50	<0.005		0.001
	87.00	88.50	D019922	1.50	<0.005		0.001
	88.50	90.00	D019923	1.50	<0.005		0.001
	90.00	91.50	D019924	1.50	<0.005		0.001
	91.50	93.00	D019925	1.50	<0.005		0.001
	93.00	94.50	D019926	1.50	<0.005		0.001
	94.50	96.00	D019928	1.50	<0.005		0.001
	96.00	97.50	D019929	1.50	<0.005		0.001
	97.50	99.00	D019930	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
106.50	121.50	SY; POR <b>Syénite; Porphyrique</b> Syénite porphyrique avec phénocristaux, Xmm à Xcm, sur ± 70% de la roche.	99.00	100.50	D019931	1.50	<0.005		0.001
			100.50	102.00	D019932	1.50	<0.005		0.001
			102.00	103.50	D019933	1.50	<0.005		0.001
			103.50	105.00	D019934	1.50	<0.005		0.001
			105.00	106.50	D019935	1.50	<0.005		0.001
			106.50	108.00	D019936	1.50	<0.005		0.001
			108.00	109.50	D019938	1.50	<0.005		0.001
			109.50	111.00	D019939	1.50	<0.005		0.001
			111.00	112.50	D019940	1.50	<0.005		0.001
			112.50	114.00	D019941	1.50	<0.005		0.001
			114.00	115.50	D019943	1.50	<0.005		0.001
			115.50	117.00	D019944	1.50	<0.005		0.001
			117.00	118.50	D019945	1.50	<0.005		0.001
			118.50	120.00	D019946	1.50	<0.005		0.001
			120.00	121.50	D019948	1.50	<0.005		0.001
			121.50	123.00	D019949	1.50	<0.005		0.001
			123.00	124.50	D019950	1.50	<0.005		0.001
			124.50	126.00	D019951	1.50	<0.005		0.001
			126.00	127.50	D019952	1.50	<0.005		0.001
			127.50	129.00	D019953	1.50	<0.005		0.001
138.00	190.50	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains fins, porphyrique avec phénocristaux Xmm à rarement Xcm.	129.00	130.50	D019954	1.50	0.007		0.007
			130.50	132.00	D019955	1.50	<0.005		0.001
			132.00	133.50	D019956	1.50	<0.005		0.001
			133.50	135.00	D019958	1.50	<0.005		0.001
			135.00	136.50	D019959	1.50	<0.005		0.001
			136.50	138.00	D019960	1.50	<0.005		0.001
			138.00	139.50	D019961	1.50	0.005		0.005
			139.50	141.00	D019962	1.50	<0.005		0.001
			141.00	142.50	D019963	1.50	<0.005		0.001
			142.50	144.00	D019964	1.50	<0.005		0.001
144.00	145.50	D019965	1.50	<0.005		0.001			
145.50	147.00	D019966	1.50	<0.005		0.001			
147.00	148.50	D019968	1.50	0.011		0.011			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	148.50	150.00	D019969	1.50	<0.005		0.001
	150.00	151.50	D019970	1.50	<0.005		0.001
	151.50	153.00	D019971	1.50	<0.005		0.001
	153.00	154.50	D019972	1.50	0.009		0.009
	154.50	156.00	D019973	1.50	0.006		0.006
	156.00	157.50	D019974	1.50	<0.005		0.001
	157.50	159.00	D019975	1.50	<0.005		0.001
	159.00	160.50	D019976	1.50	<0.005		0.001
	160.50	162.00	D019978	1.50	<0.005		0.001
	162.00	163.50	D019979	1.50	<0.005		0.001
	163.50	165.00	D019980	1.50	<0.005		0.001
	165.00	166.50	D019981	1.50	<0.005		0.001
	166.50	168.00	D019983	1.50	<0.005		0.001
	168.00	169.50	D019984	1.50	<0.005		0.001
	169.50	171.00	D019985	1.50	0.060		0.060
	171.00	172.50	D019986	1.50	<0.005		0.001
	172.50	174.00	D019988	1.50	<0.005		0.001
	174.00	175.50	D019989	1.50	<0.005		0.001
	175.50	177.00	D019990	1.50	<0.005		0.001
	177.00	178.50	D019991	1.50	1.165		1.165
	178.50	180.00	D019992	1.50	0.045		0.045
	180.00	181.50	D019993	1.50	0.050		0.050
	181.50	183.00	D019994	1.50	0.035		0.035
	183.00	184.50	D019995	1.50	0.101		0.101
	184.50	186.00	D019996	1.50	0.011		0.011
	186.00	187.50	D019998	1.50	<0.005		0.001
	187.50	189.00	D019999	1.50	<0.005		0.001
	189.00	190.50	D020000	1.50	<0.005		0.001
	190.50	192.00	D020001	1.50	0.193		0.193
	192.00	193.50	D020002	1.50	0.019		0.019
	193.50	195.00	D020003	1.50	0.012		0.012
	195.00	196.50	D020004	1.50	0.030		0.030
	196.50	198.00	D020005	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			198.00	199.50	D020006	1.50		0.006	0.006
			199.50	201.00	D020008	1.50		<0.005	0.001
			201.00	202.50	D020009	1.50		<0.005	0.001
			202.50	204.00	D020010	1.50		<0.005	0.001
			204.00	205.50	D020011	1.50		0.009	0.009
			205.50	207.00	D020012	1.50		<0.005	0.001
			207.00	208.50	D020013	1.50		0.017	0.017
			208.50	210.00	D020014	1.50		0.009	0.009
			210.00	211.50	D020015	1.50		<0.005	0.001
			211.50	213.00	D020016	1.50		<0.005	0.001
213.00	276.00	SY; POR	213.00	214.50	D020018	1.50		<0.005	0.001
		<b>Syénite; Porphyrique</b>	214.50	216.00	D020019	1.50		<0.005	0.001
		Syénite porphyrique avec phénocristaux Xmm et rarement Xcm.	216.00	217.50	D020020	1.50		<0.005	0.001
			217.50	219.00	D020021	1.50		<0.005	0.001
			219.00	220.50	D020023	1.50		<0.005	0.001
			220.50	222.00	D020024	1.50		<0.005	0.001
			222.00	223.50	D020025	1.50		0.010	0.010
			223.50	225.00	D020026	1.50		0.033	0.033
			225.00	226.50	D020028	1.50		0.006	0.006
			226.50	228.00	D020029	1.50		<0.005	0.001
			228.00	229.50	D020030	1.50		<0.005	0.001
			229.50	231.00	D020031	1.50		0.063	0.063
			231.00	232.50	D020032	1.50		0.065	0.065
			232.50	234.00	D020033	1.50		0.015	0.015
			234.00	235.50	D020034	1.50		0.014	0.014
			235.50	237.00	D020035	1.50		<0.005	0.001
			237.00	238.50	D020036	1.50		0.009	0.009
			238.50	240.00	D020038	1.50		0.005	0.005
			240.00	241.50	D020039	1.50		<0.005	0.001
			241.50	243.00	D020040	1.50		<0.005	0.001
			243.00	244.50	D020041	1.50		0.019	0.019
			244.50	246.00	D020042	1.50		0.006	0.006
			246.00	247.50	D020043	1.50		0.005	0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	247.50	249.00	D020044	1.50	0.210		0.210
	249.00	250.50	D020045	1.50	0.030		0.030
	250.50	252.00	D020046	1.50	<0.005		0.001
	252.00	253.50	D020048	1.50	<0.005		0.001
	253.50	255.00	D020049	1.50	<0.005		0.001
	255.00	256.50	D020050	1.50	0.014		0.014
	256.50	258.00	D020051	1.50	0.039		0.039
	258.00	259.50	D020052	1.50	<0.005		0.001
	259.50	261.00	D020053	1.50	<0.005		0.001
	261.00	262.50	D020054	1.50	<0.005		0.001
	262.50	264.00	D020055	1.50	<0.005		0.001
	264.00	265.50	D020056	1.50	<0.005		0.001
	265.50	267.00	D020058	1.50	<0.005		0.001
	267.00	268.50	D020059	1.50	<0.005		0.001
	268.50	270.00	D020060	1.50	0.180		0.180
	270.00	271.50	D020061	1.50	0.007		0.007
	271.50	273.00	D020063	1.50	0.040		0.040
	273.00	274.50	D020064	1.50	0.111		0.111
	274.50	276.00	D020065	1.50	<0.005		0.001
	276.00	277.50	D020066	1.50	0.909		0.909
	277.50	279.00	D020068	1.50	0.111		0.111
	279.00	280.50	D020069	1.50	0.146		0.146
	280.50	282.00	D020070	1.50	0.086		0.086
	282.00	283.50	D020071	1.50	0.028		0.028
	283.50	285.00	D020072	1.50	0.006		0.006
	285.00	286.50	D020073	1.50	0.058		0.058
	286.50	288.00	D020074	1.50	0.011		0.011
	288.00	289.50	D020075	1.50	0.006		0.006
	289.50	291.00	D020076	1.50	<0.005		0.001
	291.00	292.50	D020078	1.50	0.376		0.376
	292.50	294.00	D020079	1.50	0.016		0.016
	294.00	295.50	D020080	1.50	0.015		0.015
	295.50	297.00	D020081	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	297.00	298.50	D020082	1.50	0.068		0.068
	298.50	300.00	D020083	1.50	0.007		0.007
	300.00	301.50	D020084	1.50	0.037		0.037
	301.50	303.00	D020085	1.50	0.014		0.014
	303.00	304.50	D020086	1.50	0.154		0.154
	304.50	306.00	D020088	1.50	0.127		0.127
	306.00	307.50	D020089	1.50	0.014		0.014
	307.50	309.00	D020090	1.50	0.457		0.457
	309.00	310.50	D020091	1.50	0.697		0.697
	310.50	312.00	D020092	1.50	0.013		0.013
	312.00	313.50	D020093	1.50	0.043		0.043
	313.50	315.00	D020094	1.50	<0.005		0.001
	315.00	316.50	D020095	1.50	0.165		0.165
	316.50	318.00	D020096	1.50	0.218		0.218
	318.00	319.50	D020098	1.50	0.136		0.136
	319.50	321.00	D020099	1.50	0.208		0.208
	321.00	322.50	D020100	1.50	0.020		0.020
	322.50	324.00	D020101	1.50	0.282		0.282
	324.00	325.50	D020103	1.50	<0.005		0.001
	325.50	327.00	D020104	1.50	<0.005		0.001
	327.00	328.50	D020105	1.50	<0.005		0.001
	328.50	330.00	D020106	1.50	<0.005		0.001
	330.00	331.50	D020108	1.50	<0.005		0.001
	331.50	333.00	D020109	1.50	0.005		0.005
	333.00	334.50	D020110	1.50	0.189		0.189
	334.50	336.00	D020111	1.50	0.135		0.135
	336.00	337.00	D020112	1.00	0.019		0.019
	337.00	338.50	D020113	1.50	<0.005		0.001
	338.50	340.00	D020114	1.50	<0.005		0.001
	340.00	341.50	D020115	1.50	<0.005		0.001
	341.50	343.00	D020116	1.50	0.015		0.015
	343.00	344.50	D020118	1.50	<0.005		0.001
	344.50	346.00	D020119	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	346.00	347.50	D020120	1.50	0.021		0.021
	347.50	349.00	D020121	1.50	<0.005		0.001
	349.00	350.50	D020122	1.50	<0.005		0.001
	350.50	352.00	D020123	1.50	<0.005		0.001
	352.00	353.50	D020124	1.50	0.195		0.195
	353.50	355.00	D020125	1.50	0.035		0.035
	355.00	356.50	D020126	1.50	0.012		0.012
	356.50	358.00	D020128	1.50	0.046		0.046
	358.00	359.50	D020129	1.50	0.026		0.026
	359.50	361.00	D020130	1.50	0.047		0.047
	361.00	362.50	D020131	1.50	0.043		0.043
	362.50	364.00	D020132	1.50	0.005		0.005
	364.00	365.50	D020133	1.50	0.027		0.027
	365.50	367.00	D020134	1.50	0.017		0.017
	367.00	368.50	D020135	1.50	0.008		0.008
	368.50	370.00	D020136	1.50	0.008		0.008
	370.00	371.50	D020138	1.50	0.027		0.027
	371.50	373.00	D020139	1.50	<0.005		0.001
	373.00	374.50	D020140	1.50	0.005		0.005
	374.50	376.00	D020141	1.50	<0.005		0.001
	376.00	377.50	D020143	1.50	0.107		0.107
	377.50	379.00	D020144	1.50	0.045		0.045
	379.00	380.00	D020145	1.00	<0.005		0.001
	380.00	381.00	D020146	1.00	<0.005		0.001
	381.00	382.50	D020148	1.50	0.027		0.027
	382.50	384.00	D020149	1.50	0.165		0.165
	384.00	385.50	D020150	1.50	0.119		0.119
	385.50	387.00	D020151	1.50	2.170		2.170
	387.00	388.20	D020152	1.20	3.500		3.500
	388.20	389.50	D020153	1.30	0.473		0.473
	389.50	391.00	D020154	1.50	0.494		0.494
	391.00	392.50	D020155	1.50	0.926		0.926
	392.50	394.00	D020156	1.50	0.024		0.024

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	394.00	395.50	D020158	1.50	0.335		0.335
	395.50	397.00	D020159	1.50	0.558		0.558
	397.00	398.50	D020160	1.50	0.007		0.007
	398.50	400.00	D020161	1.50	<0.005		0.001
	400.00	401.50	D020162	1.50	0.008		0.008
	401.50	403.00	D020163	1.50	<0.005		0.001
	403.00	404.50	D020164	1.50	<0.005		0.001
	404.50	406.00	D020165	1.50	<0.005		0.001
	406.00	407.50	D020166	1.50	<0.005		0.001
	407.50	409.00	D020168	1.50	<0.005		0.001
	409.00	410.50	D020169	1.50	<0.005		0.001
	410.50	412.00	D020170	1.50	<0.005		0.001
	412.00	413.50	D020171	1.50	0.015		0.015
	413.50	415.00	D020172	1.50	0.111		0.111
	415.00	416.50	D020173	1.50	0.290		0.290
	416.50	418.00	D020174	1.50	1.910		1.910
	418.00	419.50	D020175	1.50	0.433		0.433
	419.50	421.00	D020176	1.50	<0.005		0.001
	421.00	422.50	D020178	1.50	<0.005		0.001
	422.50	424.00	D020179	1.50	0.062		0.062
	424.00	425.00	D020180	1.00	<0.005		0.001
	425.00	426.00	D020181	1.00	<0.005		0.001
	426.00	427.50	D020183	1.50	0.019		0.019
	427.50	429.00	D020184	1.50	0.023		0.023
	429.00	430.50	D020185	1.50	0.015		0.015
	430.50	432.00	D020186	1.50	0.014		0.014
	432.00	433.50	D020188	1.50	<0.005		0.001
	433.50	435.00	D020189	1.50	<0.005		0.001
	435.00	436.50	D020190	1.50	<0.005		0.001
	436.50	438.00	D020191	1.50	0.032		0.032
	438.00	439.50	D020192	1.50	<0.005		0.001
	439.50	441.00	D020193	1.50	0.042		0.042
	441.00	442.50	D020194	1.50	0.193		0.193

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	442.50	444.00	D020195	1.50	<0.005		0.001
	444.00	445.50	D020196	1.50	<0.005		0.001
	445.50	447.00	D020198	1.50	<0.005		0.001
	447.00	448.50	D020199	1.50	0.189		0.189
	448.50	450.00	D020200	1.50	0.194		0.194
	450.00	451.50	D020201	1.50	0.006		0.006
	451.50	453.00	D020203	1.50	<0.005		0.001
	453.00	454.50	D020204	1.50	0.378		0.378
	454.50	456.00	D020205	1.50	0.322		0.322
	456.00	457.50	D020206	1.50	0.117		0.117
	457.50	459.00	D020208	1.50	1.565		1.565
	459.00	460.50	D020209	1.50	1.110		1.110
	460.50	462.00	D020210	1.50	0.233		0.233
	462.00	463.50	D020211	1.50	0.597		0.597
	463.50	465.00	D020212	1.50	1.075		1.075
	465.00	466.50	D020213	1.50	0.570		0.570
	466.50	468.00	D020214	1.50	<0.005		0.001
	468.00	469.50	D020215	1.50	0.006		0.006
	469.50	471.00	D020216	1.50	0.007		0.007
	471.00	472.50	D020218	1.50	0.005		0.005
	472.50	474.00	D020219	1.50	0.019		0.019
	474.00	475.50	D020220	1.50	<0.005		0.001
	475.50	477.00	D020221	1.50	<0.005		0.001
	477.00	478.50	D020222	1.50	<0.005		0.001
	478.50	480.00	D020223	1.50	0.005		0.005
	480.00	481.00	D020224	1.00	<0.005		0.001
	481.00	482.00	D020225	1.00	<0.005		0.001
482.00	Fin du sondage						
	Nombre d'échantillons : 323						
	Nombre d'échantillons QAQC : 47						
	Longueur totale échantillonnée : 480.70						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
1.30	3.00	D019857	D019856	1.70	<0.005	0.001
7.50	7.50	D019862	M1	0.00	<0.005	0.001
13.50	13.50	D019867	L	0.00	2.110	2.110
27.00	28.50	D019877	D019876	1.50	<0.005	0.001
40.50	40.50	D019887	M	0.00	3.240	3.240
54.00	55.50	D019897	D019896	1.50	<0.005	0.001
60.00	60.00	D019902	M1	0.00	0.006	0.006
66.00	66.00	D019907	J	0.00	0.799	0.799
79.50	81.00	D019917	D019916	1.50	<0.005	0.001
93.00	93.00	D019927	K	0.00	1.115	1.115
106.50	108.00	D019937	D019936	1.50	<0.005	0.001
112.50	112.50	D019942	M1	0.00	0.007	0.007
118.50	118.50	D019947	L	0.00	2.310	2.310
132.00	133.50	D019957	D019956	1.50	<0.005	0.001
145.50	145.50	D019967	M	0.00	3.160	3.160
159.00	160.50	D019977	D019976	1.50	<0.005	0.001
165.00	165.00	D019982	M1	0.00	<0.005	0.001
171.00	171.00	D019987	J	0.00	0.779	0.779
184.50	186.00	D019997	D019996	1.50	0.013	0.013
198.00	198.00	D020007	K	0.00	1.020	1.020
211.50	213.00	D020017	D020016	1.50	<0.005	0.001
217.50	217.50	D020022	M1	0.00	0.005	0.005
223.50	223.50	D020027	L	0.00	2.180	2.180
237.00	238.50	D020037	D020036	1.50	0.008	0.008
250.50	250.50	D020047	M	0.00	3.320	3.320
264.00	265.50	D020057	D020056	1.50	<0.005	0.001
270.00	270.00	D020062	M1	0.00	<0.005	0.001
276.00	276.00	D020067	J	0.00	0.770	0.770
289.50	291.00	D020077	D020076	1.50	<0.005	0.001
303.00	303.00	D020087	K	0.00	1.130	1.130
316.50	318.00	D020097	D020096	1.50	0.309	0.309
322.50	322.50	D020102	M1	0.00	<0.005	0.001
328.50	328.50	D020107	L	0.00	2.180	2.180

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
341.50	343.00	D020117	D020116	1.50	0.025	0.025
355.00	355.00	D020127	M	0.00	3.290	3.290
368.50	370.00	D020137	D020136	1.50	0.008	0.008
374.50	374.50	D020142	M1	0.00	0.008	0.008
380.00	380.00	D020147	J	0.00	0.731	0.731
392.50	394.00	D020157	D020156	1.50	0.024	0.024
406.00	406.00	D020167	K	0.00	1.030	1.030
419.50	421.00	D020177	D020176	1.50	0.006	0.006
425.00	425.00	D020182	M1	0.00	<0.005	0.001
430.50	430.50	D020187	L	0.00	2.210	2.210
444.00	445.50	D020197	D020196	1.50	<0.005	0.001
450.00	450.00	D020202	M1	0.00	<0.005	0.001
456.00	456.00	D020207	J	0.00	0.752	0.752
469.50	471.00	D020217	D020216	1.50	0.007	0.007



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	181.40°	-42.70°	Non	Reflex	173.00	182.50°	-43.70°	Non
Reflex	77.00	180.50°	-44.10°	Non	Reflex	176.00	182.60°	-43.70°	Non
Reflex	80.00	177.60°	-44.00°	Oui	Reflex	179.00	182.80°	-43.70°	Non
Reflex	83.00	181.40°	-44.00°	Non	Reflex	182.00	182.90°	-43.70°	Non
Reflex	86.00	179.70°	-44.00°	Non	Reflex	185.00	182.90°	-43.70°	Non
Reflex	89.00	180.10°	-44.00°	Non	Reflex	188.00	183.40°	-43.60°	Non
Reflex	92.00	181.30°	-44.00°	Non	Reflex	191.00	183.30°	-43.80°	Non
Reflex	95.00	180.80°	-43.80°	Non					
Reflex	98.00	182.30°	-44.00°	Oui					
Reflex	101.00	181.40°	-44.00°	Non					
Reflex	104.00	180.00°	-43.70°	Non					
Reflex	107.00	180.90°	-43.50°	Non					
Reflex	110.00	182.90°	-44.00°	Non					
Reflex	113.00	181.70°	-44.00°	Non					
Reflex	116.00	184.90°	-44.00°	Oui					
Reflex	119.00	182.20°	-44.00°	Non					
Reflex	122.00	181.80°	-44.00°	Non					
Reflex	125.00	181.60°	-45.20°	Non					
Reflex	128.00	182.50°	-44.70°	Non					
Reflex	131.00	179.70°	-45.00°	Oui					
Reflex	134.00	181.50°	-43.40°	Non					
Reflex	137.00	181.60°	-43.90°	Non					
Reflex	140.00	183.20°	-43.90°	Non					
Reflex	143.00	180.70°	-42.00°	Non					
Reflex	146.00	181.50°	-43.90°	Non					
Reflex	149.00	181.00°	-43.80°	Non					
Reflex	152.00	184.00°	-43.40°	Oui					
Reflex	155.00	190.40°	-43.50°	Oui					
Reflex	158.00	181.90°	-43.90°	Non					
Reflex	161.00	181.20°	-43.70°	Non					
Reflex	164.00	181.60°	-43.90°	Non					
Reflex	167.00	178.10°	-42.30°	Oui					
Reflex	170.00	182.60°	-43.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	3.00	MT <b>Mort-terrain</b> MT							
3.00	120.40	SY; POR <b>Syénite 55*; Porphyrique</b> syénite porphyrique à cristaux de feldspath; modérément hématisée; les cristaux de feldspath sont couvent rempli de chlorite et contenant de la magnétite; pyrite disséminée dans la matrice; les cheveux et les veinules sont souvent chloritisés et sont en network;  les zones silicifiées contiennent de la pyrite disséminé entre 0,5% et 0,8% entre 52,7m à 54,7m;	3.00	4.00	D034173	1.00	0.044		0.044
			4.00	5.00	D034174	1.00	<0.005		0.001
			5.00	6.50	D034175	1.50	<0.005		0.001
			6.50	8.00	D034176	1.50	<0.005		0.001
			8.00	9.50	D034177	1.50	<0.005		0.001
			9.50	11.00	D034178	1.50	<0.005		0.001
			11.00	12.50	D034179	1.50	<0.005		0.001
			12.50	14.00	D034181	1.50	0.005		0.005
			14.00	15.50	D034182	1.50	0.020		0.020
			15.50	17.00	D034183	1.50	<0.005		0.001
			17.00	18.50	D034184	1.50	<0.005		0.001
			18.50	20.00	D034185	1.50	<0.005		0.001
			20.00	21.50	D034186	1.50	<0.005		0.001
			21.50	23.00	D034187	1.50	<0.005		0.001
			23.00	24.50	D034188	1.50	<0.005		0.001
			24.50	26.00	D034189	1.50	0.011		0.011
			26.00	27.50	D034191	1.50	<0.005		0.001
			27.50	29.00	D034193	1.50	<0.005		0.001
			29.00	30.50	D034194	1.50	0.308		0.308
			30.50	32.00	D034195	1.50	<0.005		0.001
			32.00	33.50	D034196	1.50	<0.005		0.001
			33.50	35.00	D034197	1.50	<0.005		0.001
			35.00	36.50	D034198	1.50	<0.005		0.001
			36.50	38.00	D034199	1.50	0.189		0.189
			38.00	39.50	D034201	1.50	0.029		0.029
			39.50	41.00	D034202	1.50	0.100		0.100
			41.00	42.50	D034203	1.50	0.247		0.247
			42.50	44.00	D034204	1.50	0.035		0.035
			44.00	45.50	D034205	1.50	0.139		0.139
			45.50	47.00	D034206	1.50	0.005		0.005
			47.00	48.50	D034207	1.50	0.187		0.187

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			48.50	50.00	D034208	1.50		0.061		
			50.00	51.50	D034209	1.50		0.110		0.110
			51.50	52.70	D034211	1.20		0.467		0.467
3.00	52.70	HM05 <b>Hématisé 5</b> modérément hématisé								
52.70	54.70	SI04 <b>Silicifié 4</b> plus ou moins à modérément silicifié;	52.70	53.70	D034212	1.00		3.710		3.710
			53.70	54.70	D034213	1.00		2.880		2.880
54.70	120.40	HM05 <b>Hématisé 5</b> modérément hématisé	54.70	56.00	D034214	1.30		0.382		0.382
			56.00	57.50	D034215	1.50		0.256		0.256
			57.50	59.00	D034216	1.50		0.585		0.585
			59.00	60.50	D034217	1.50		2.030		2.030
			60.50	62.00	D034218	1.50		2.780		2.780
			62.00	63.50	D034219	1.50		2.970		2.970
			63.50	65.00	D034221	1.50		0.006		0.006
			65.00	66.50	D034222	1.50		0.068		0.068
			66.50	68.00	D034223	1.50		0.010		0.010
			68.00	69.50	D034224	1.50		0.074		0.074
			69.50	71.00	D034225	1.50		0.161		0.161
			71.00	72.50	D034226	1.50		0.081		0.081
			72.50	74.00	D034227	1.50		0.082		0.082
			74.00	75.50	D034228	1.50		0.053		0.053
			75.50	77.00	D034229	1.50		<0.005		0.001
			77.00	78.50	D034231	1.50		0.032		0.032
			78.50	80.00	D034233	1.50		0.016		0.016
			80.00	81.50	D034234	1.50		<0.005		0.001
			81.50	83.00	D034235	1.50		0.051		0.051
			83.00	84.50	D034236	1.50		0.054		0.054
			84.50	86.00	D034237	1.50		1.005		1.005
			86.00	87.50	D034238	1.50		0.504		0.504
			87.50	89.00	D034239	1.50		0.267		0.267
			89.00	90.50	D034241	1.50		0.187		0.187
			90.50	92.00	D034242	1.50		0.133		0.133

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				92.00	93.50	D034243	1.50	0.016		0.016
				93.50	95.00	D034244	1.50	0.260		0.260
				95.00	96.50	D034245	1.50	0.021		0.021
				96.50	98.00	D034246	1.50	0.076		0.076
				98.00	99.50	D034247	1.50	0.112		0.112
				99.50	101.00	D034248	1.50	0.056		0.056
				101.00	102.50	D034249	1.50	0.217		0.217
				102.50	104.00	D034251	1.50	0.091		0.091
				104.00	105.50	D034252	1.50	0.064		0.064
				105.50	107.00	D034253	1.50	0.218		0.218
				107.00	108.50	D034254	1.50	0.106		0.106
				108.50	110.00	D034255	1.50	0.572		0.572
				110.00	111.50	D034256	1.50	0.243		0.243
				111.50	113.00	D034257	1.50	0.298		0.298
				113.00	114.50	D034258	1.50	0.040		0.040
				114.50	116.00	D034259	1.50	0.606		0.606
				116.00	117.50	D034261	1.50	0.074		0.074
				117.50	119.00	D034262	1.50	0.229		0.229
				119.00	120.35	D034263	1.35	0.033		0.033
120.35	127.70	Py00.8 <b>Pyrite 0.8%</b> pyrite disséminé entre 0,5 et 0,8%		120.35	122.00	D034264	1.65	1.220		1.220
120.40	127.70	SY; POR <b>Syénite 70°; Porphyrique</b> syénite porphyrique avec des cristaux de feldspath; zone modérément silicifiée et peu chloritisée; cristaux très fin de pyrite disséminé entre 0,5% et 0,8%; les veinules et les cheveux de quartz sont en network;								
120.40	127.70	SI04 <b>Silicifié 4</b> plus ou moins à modérément silicifié;		122.00	123.50	D034265	1.50	1.665		1.665
				123.50	125.00	D034266	1.50	1.365		1.365
				125.00	126.50	D034267	1.50	4.290		4.290
				126.50	127.70	D034268	1.20	2.190		2.190
127.70	143.00	ST; POR <b>Siltstone 50°; Porphyrique</b> syénite porphyrique à cristaux de feldspath; modérément hématisée; les cristaux de feldspath sont couvent rempli de chlorite et contenant								

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
de la magnétite; pyrite disséminée dans la matrice; les cheveux et les veinules sont souvent chloritisés et sont en network;								
127.70	143.00	HM05	127.70	129.40	D034269	1.70	0.049	0.049
		<b>Hématisé 5</b>	129.40	131.00	D034271	1.60	<0.005	0.001
		modérément hématisé et plus ou moins chloriteux	131.00	132.50	D034273	1.50	<0.005	0.001
			132.50	134.00	D034274	1.50	0.181	0.181
			134.00	135.50	D034275	1.50	<0.005	0.001
			135.50	137.00	D034276	1.50	0.010	0.010
			137.00	138.50	D034277	1.50	0.132	0.132
			138.50	140.00	D034278	1.50	<0.005	0.001
			140.00	141.00	D034279	1.00	<0.005	0.001
			141.00	141.90	D034281	0.90	0.007	0.007
			141.90	143.00	D034282	1.10	0.077	0.077
143.00	145.50	BA; FIN	143.00	144.50	D034283	1.50	<0.005	0.001
		<b>Basalte 50°; Grains fins</b>	144.50	145.50	D034284	1.00	<0.005	0.001
		dyke de Basalte andésitique et phanéritique, aux contacts foliés et graduels avec la syénite; pyrite disséminé dans la matrice;						
145.50	154.80	SY; POR						
		<b>Syénite 55°; Porphyrique</b>						
		syénite peu porphyrique à cristaux de feldspath; plus ou moins hématisée et plus ou moins chloritisé; les cristaux de feldspath sont couverts remplis de chlorite; pyrite disséminée dans la matrice; les cheveux et les veinules sont souvent chloritisés et sont en network;						
145.50	156.50	CH03; HM	145.50	147.00	D034285	1.50	0.013	0.013
		<b>Chloriteux 3; Hématisé</b>	147.00	148.00	D034286	1.00	<0.005	0.001
		plus ou moins hématisé et plus ou moins chloriteux	148.00	149.00	D034287	1.00	<0.005	0.001
			149.00	150.50	D034288	1.50	0.006	0.006
			150.50	152.00	D034289	1.50	0.061	0.061
			152.00	153.50	D034291	1.50	0.147	0.147
153.50	179.00	Py00.8	153.50	154.80	D034292	1.30	0.080	0.080
		<b>Pyrite 0.8%</b>						
		pyrite disséminée entre 0,5% et 0,8%						
154.80	168.00	BA	154.80	156.50	D034293	1.70	0.034	0.034
		<b>Basalte 50°</b>						
		Basalte andésitique; pyrite disséminée entre 0,5% et 0,8% dans la zone de contact avec la syénite, dans une intersection de sediment						



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
entre 164m et 164.60m et dans la zone de contact avec les sédiments;								
156.50	179.00	CB05	156.50	158.00	D034294	1.50	0.022	0.022
		<b>Carbonaté 5</b>	158.00	159.50	D034295	1.50	0.047	0.047
		modérément carbonaté;	159.50	161.00	D034296	1.50	0.041	0.041
			161.00	162.50	D034297	1.50	0.017	0.017
			162.50	164.00	D034298	1.50	0.018	0.018
			164.00	165.50	D034299	1.50	0.099	0.099
			165.50	167.00	D034301	1.50	0.015	0.015
			167.00	168.00	D034302	1.00	0.005	0.005
168.00	179.00	BA	168.00	169.00	D034303	1.00	0.007	0.007
		<b>Basalte 45°</b>	169.00	170.00	D034304	1.00	<0.005	0.001
		basalte scissailé à 45°AC, modérément carbonaté; pyrite disséminé	170.00	171.50	D034305	1.50	0.007	0.007
		entre du 0,2% et 0,5%; zone de veinules de quartz-calcite 10%;	171.50	173.00	D034306	1.50	<0.005	0.001
			173.00	174.50	D034307	1.50	<0.005	0.001
			174.50	176.00	D034308	1.50	<0.005	0.001
			176.00	177.50	D034309	1.50	<0.005	0.001
			177.50	179.00	D034311	1.50	0.010	0.010
179.00	187.30	MS						
		<b>Mudstone 45°</b>						
		mudstone modérément carbonatée et plus ou moins chloritisée, et dont						
		le litage (entre 30°AC et 45°AC) est marqué par les veinules de						
		quartz-calcite et les veinules de graphite; la pyrite disséminé jusuq'à						
		2%;						
179.00	191.00	CB05; CH03	179.00	180.50	D034313	1.50	<0.005	0.001
		<b>Carbonaté 5; Chloriteux 3</b>	180.50	182.00	D034314	1.50	<0.005	0.001
		modérément carbonaté et plus ou moins chloriteux;	182.00	183.50	D034315	1.50	<0.005	0.001
			183.50	185.00	D034316	1.50	0.011	0.011
184.00	189.00	CIS	185.00	186.50	D034317	1.50	0.005	0.005
		<b>Cisaillement 45°</b>	186.50	188.00	D034318	1.50	0.005	0.005
		zone de cisaillement 45°AC;						
187.30	187.70	NR						
		<b>Carotte perdue</b>						
		LOST						
187.70	191.00	MS	188.00	189.50	D034319	1.50	<0.005	0.001
		<b>Mudstone 45°</b>	189.50	191.00	D034321	1.50	<0.005	0.001
		mudstone modérément carbonatée et plus ou moins chloritisée, et dont						

## Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
le litage (entre 30°AC et 45°AC) est marqué par les veinules de quartz-calite et les veinules de graphite; la pyrite disséminé jusuq'à 2%;							
<b>191.00</b> <b>Fin du sondage</b> Nombre d'échantillons : 130 Nombre d'échantillons QAQC : 19 Longueur totale échantillonnée : 188.00							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
11.00	12.50	D034180	D034179	1.50	<0.005	0.001
24.50	24.50	D034190	L	0.00	2.110	2.110
26.00	26.00	D034192	M1	0.00	<0.005	0.001
36.50	38.00	D034200	D034199	1.50	0.111	0.111
50.00	50.00	D034210	M	0.00	2.900	2.900
62.00	63.50	D034220	D034219	1.50	3.020	3.020
75.50	75.50	D034230	J	0.00	0.793	0.793
77.00	77.00	D034232	M1	0.00	<0.005	0.001
87.50	89.00	D034240	D034239	1.50	0.267	0.267
101.00	101.00	D034250	K	0.00	1.035	1.035
114.50	116.00	D034260	D034259	1.50	0.614	0.614
127.70	127.70	D034270	L	0.00	2.020	2.020
129.40	129.40	D034272	M1	0.00	<0.005	0.001
140.00	141.00	D034280	D034279	1.00	0.005	0.005
150.50	150.50	D034290	M	0.00	3.000	3.000
164.00	165.50	D034300	D034299	1.50	0.102	0.102
176.00	176.00	D034310	J	0.00	0.765	0.765
177.50	177.50	D034312	M1	0.00	<0.005	0.001
188.00	189.50	D034320	D034319	1.50	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> BD10-227	Titre minier :	Section :	629900
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : David RUHARA	Du : 2010-05-10	Date de description :	
	Au : 2010-05-12		

Collet

Azimut : 0.00°		UTM
Plongée : -57.00°	Est	629 899.9
Longueur : 260.00 m	Nord	5 374 386.7
	Élévation	279.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui	Reflex	38.00	357.80°	-57.20°	Non
Reflex	5.00	340.60°	-57.00°	Oui	Reflex	41.00	357.50°	-57.20°	Non
Reflex	8.00	340.60°	-57.10°	Oui	Reflex	44.00	357.30°	-57.20°	Non
Reflex	11.00	0.40°	-56.40°	Oui	Reflex	47.00	357.10°	-57.20°	Non
Reflex	14.00	303.10°	-56.70°	Oui	Reflex	50.00	357.10°	-57.10°	Non
Reflex	17.00	330.40°	-57.00°	Oui	Reflex	53.00	357.00°	-57.00°	Non
Reflex	20.00	348.90°	-57.30°	Oui	Reflex	56.00	356.50°	-56.50°	Non
Reflex	23.00	344.70°	-57.50°	Oui	Reflex	59.00	356.90°	-57.00°	Non
Reflex	26.00	353.40°	-57.50°	Oui	Reflex	62.00	356.60°	-57.00°	Non
Reflex	29.00	356.20°	-57.50°	Non	Reflex	65.00	356.50°	-57.00°	Non
Reflex	32.00	356.50°	-55.70°	Non	Reflex	68.00	356.50°	-56.90°	Non
Reflex	35.00	357.70°	-57.30°	Non	Reflex	71.00	356.00°	-57.00°	Non

Description

Dimension de la carotte : NQ	Cimenté : Non	Entreposé : Oui
------------------------------	---------------	-----------------

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	356.80°	-56.60°	Non	Reflex	173.00	353.90°	-47.10°	Oui
Reflex	77.00	356.30°	-56.90°	Non	Reflex	176.00	359.00°	-56.10°	Non
Reflex	80.00	357.80°	-56.90°	Non	Reflex	179.00	359.20°	-56.00°	Non
Reflex	83.00	356.80°	-56.80°	Non	Reflex	182.00	359.30°	-56.10°	Non
Reflex	86.00	357.90°	-55.30°	Non	Reflex	185.00	359.60°	-56.10°	Non
Reflex	89.00	356.50°	-56.80°	Non	Reflex	188.00	359.60°	-56.10°	Non
Reflex	92.00	355.50°	-55.10°	Non	Reflex	191.00	359.70°	-56.00°	Non
Reflex	95.00	356.10°	-56.70°	Non	Reflex	194.00	359.80°	-56.00°	Non
Reflex	98.00	356.20°	-56.70°	Non	Reflex	197.00	0.10°	-55.90°	Non
Reflex	101.00	356.10°	-56.70°	Non	Reflex	200.00	0.10°	-55.80°	Non
Reflex	104.00	355.90°	-56.70°	Non	Reflex	203.00	0.40°	-55.90°	Non
Reflex	107.00	356.30°	-56.90°	Non	Reflex	206.00	0.60°	-55.90°	Non
Reflex	110.00	355.10°	-54.50°	Non	Reflex	209.00	0.60°	-55.90°	Non
Reflex	113.00	356.20°	-56.60°	Non	Reflex	212.00	1.80°	-57.20°	Oui
Reflex	116.00	356.10°	-56.60°	Non	Reflex	215.00	0.80°	-55.90°	Non
Reflex	119.00	356.10°	-56.50°	Non	Reflex	218.00	0.60°	-56.00°	Non
Reflex	122.00	356.30°	-56.50°	Non	Reflex	221.00	0.20°	-56.00°	Non
Reflex	125.00	356.40°	-56.40°	Non	Reflex	224.00	2.10°	-56.00°	Oui
Reflex	128.00	356.50°	-56.40°	Non	Reflex	227.00	1.20°	-56.00°	Non
Reflex	131.00	356.70°	-56.30°	Non	Reflex	230.00	1.00°	-56.10°	Non
Reflex	134.00	356.90°	-56.30°	Non	Reflex	233.00	1.50°	-56.00°	Non
Reflex	137.00	357.10°	-56.20°	Non	Reflex	236.00	1.90°	-56.00°	Non
Reflex	140.00	357.00°	-56.10°	Non	Reflex	239.00	1.90°	-56.00°	Non
Reflex	143.00	357.10°	-56.10°	Non	Reflex	242.00	1.40°	-55.90°	Non
Reflex	146.00	357.20°	-56.10°	Non	Reflex	245.00	1.20°	-55.80°	Non
Reflex	149.00	357.50°	-56.10°	Non	Reflex	248.00	1.20°	-55.60°	Non
Reflex	152.00	357.70°	-56.10°	Non	Reflex	251.00	1.60°	-55.70°	Non
Reflex	155.00	357.70°	-56.10°	Non	Reflex	254.00	1.60°	-55.50°	Non
Reflex	158.00	358.00°	-56.20°	Non	Reflex	257.00	1.60°	-55.50°	Non
Reflex	161.00	358.10°	-56.20°	Non	Reflex	260.00	1.80°	-55.50°	Non
Reflex	164.00	358.30°	-56.10°	Non					
Reflex	167.00	358.50°	-56.20°	Non					
Reflex	170.00	358.70°	-56.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	26.60	MT						
		<b>Mort-terrain</b>						
26.60	75.20	BA; FIN; AMY	26.60	28.00	D018421	1.40	<0.005	0.001
		<b>Basalte; Grains fins; Amygdalaire</b>	28.00	29.50	D018423	1.50	<0.005	0.001
		Basalte massive, à grains et amygdalaire.	29.50	31.00	D018424	1.50	<0.005	0.001
			31.00	32.50	D018425	1.50	<0.005	0.001
			32.50	34.00	D018426	1.50	<0.005	0.001
			34.00	35.50	D018428	1.50	<0.005	0.001
			35.50	37.00	D018429	1.50	<0.005	0.001
			37.00	38.50	D018430	1.50	<0.005	0.001
			38.50	40.00	D018431	1.50	<0.005	0.001
			40.00	41.50	D018432	1.50	<0.005	0.001
			41.50	43.00	D018433	1.50	<0.005	0.001
			43.00	44.50	D018434	1.50	<0.005	0.001
			44.50	46.00	D018435	1.50	<0.005	0.001
			46.00	47.50	D018436	1.50	<0.005	0.001
			47.50	49.00	D018438	1.50	<0.005	0.001
			49.00	50.50	D018439	1.50	<0.005	0.001
			50.50	52.00	D018440	1.50	<0.005	0.001
			52.00	53.50	D018441	1.50	<0.005	0.001
			53.50	55.00	D018442	1.50	<0.005	0.001
			55.00	56.50	D018443	1.50	<0.005	0.001
			56.50	58.00	D018444	1.50	<0.005	0.001
			58.00	59.50	D018445	1.50	<0.005	0.001
			59.50	61.00	D018446	1.50	<0.005	0.001
			61.00	62.50	D018448	1.50	<0.005	0.001
			62.50	64.00	D018449	1.50	<0.005	0.001
			64.00	65.50	D018450	1.50	<0.005	0.001
			65.50	67.00	D018451	1.50	<0.005	0.001
			67.00	68.50	D018452	1.50	<0.005	0.001
			68.50	70.00	D018453	1.50	<0.005	0.001
			70.00	71.50	D018454	1.50	<0.005	0.001
			71.50	73.00	D018455	1.50	<0.005	0.001
			73.00	74.00	D018456	1.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
75.20	84.30	SY; FIN; POR <b>Syénite 55°; Grains fins; Porphyrique</b> Syénite à grains fins et porphyrique avec de phénocristaux Xmm à Xcm.	74.00	75.20	D018458	1.20	<0.005		0.001
			75.20	76.50	D018459	1.30	0.010		0.010
			76.50	78.00	D018460	1.50	<0.005		0.001
			78.00	79.50	D018461	1.50	<0.005		0.001
			79.50	81.00	D018463	1.50	<0.005		0.001
			81.00	82.60	D018464	1.60	<0.005		0.001
			82.60	84.30	D018465	1.70	<0.005		0.001
84.30	130.50	BA; MAS; FIN; AMY <b>Basalte; Roche massive; Grains fins; Amygdalaire</b> Basalte massive, à grains, avec passage amygdalaire.	84.30	85.50	D018466	1.20	0.005		0.005
			85.50	87.00	D018468	1.50	<0.005		0.001
			87.00	88.50	D018469	1.50	<0.005		0.001
			88.50	90.00	D018470	1.50	<0.005		0.001
			90.00	91.50	D018471	1.50	<0.005		0.001
			91.50	93.00	D018472	1.50	<0.005		0.001
			93.00	94.50	D018473	1.50	<0.005		0.001
			94.50	96.00	D018474	1.50	<0.005		0.001
			96.00	97.50	D018475	1.50	<0.005		0.001
			97.50	99.00	D018476	1.50	<0.005		0.001
			99.00	100.50	D018478	1.50	<0.005		0.001
			100.50	102.00	D018479	1.50	<0.005		0.001
			102.00	103.50	D018480	1.50	<0.005		0.001
			103.50	105.00	D018481	1.50	<0.005		0.001
			105.00	106.50	D018482	1.50	<0.005		0.001
			106.50	108.00	D018483	1.50	0.010		0.010
			108.00	109.50	D018484	1.50	0.006		0.006
109.50	111.00	D018485	1.50	<0.005		0.001			
111.00	112.50	D018486	1.50	<0.005		0.001			
112.50	114.00	D018488	1.50	<0.005		0.001			
114.00	115.50	D018489	1.50	<0.005		0.001			
115.50	117.00	D018490	1.50	<0.005		0.001			
117.00	118.50	D018491	1.50	<0.005		0.001			
118.50	120.00	D018492	1.50	<0.005		0.001			
120.00	121.50	D018493	1.50	<0.005		0.001			
121.50	123.00	D018494	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
130.50	193.10	GA; FIN; MTY <b>Gabbro; Grains fins; Grains moyens</b> Gabbroïque à grains fins à moyens.	123.00	124.50	D018495	1.50	<0.005		0.001
			124.50	126.00	D018496	1.50	<0.005		0.001
			126.00	127.50	D018498	1.50	<0.005		0.001
			127.50	129.00	D018499	1.50	<0.005		0.001
			129.00	130.50	D018500	1.50	<0.005		0.001
			130.50	132.00	D018501	1.50	<0.005		0.001
			132.00	133.50	D018503	1.50	<0.005		0.001
			133.50	135.00	D018504	1.50	<0.005		0.001
			135.00	136.50	D018505	1.50	<0.005		0.001
			136.50	138.00	D018506	1.50	<0.005		0.001
			138.00	139.50	D018508	1.50	<0.005		0.001
			139.50	141.00	D018509	1.50	<0.005		0.001
			141.00	142.50	D018510	1.50	<0.005		0.001
			142.50	144.00	D018511	1.50	<0.005		0.001
			144.00	145.50	D018512	1.50	<0.005		0.001
			145.50	147.00	D018513	1.50	<0.005		0.001
			147.00	148.50	D018514	1.50	<0.005		0.001
			148.50	150.00	D018515	1.50	<0.005		0.001
			150.00	151.50	D018516	1.50	<0.005		0.001
			151.50	153.00	D018518	1.50	<0.005		0.001
			153.00	154.50	D018519	1.50	0.015		0.015
			154.50	156.00	D018520	1.50	0.012		0.012
			156.00	157.50	D018521	1.50	<0.005		0.001
			157.50	159.00	D018522	1.50	<0.005		0.001
			159.00	160.50	D018523	1.50	<0.005		0.001
			160.50	162.00	D018524	1.50	<0.005		0.001
			162.00	163.50	D018525	1.50	0.012		0.012
163.50	165.00	D018526	1.50	<0.005		0.001			
165.00	166.50	D018528	1.50	0.011		0.011			
166.50	168.00	D018529	1.50	0.052		0.052			
168.00	169.50	D018530	1.50	<0.005		0.001			
169.50	171.00	D018531	1.50	<0.005		0.001			
171.00	172.50	D018532	1.50	<0.005		0.001			



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			172.50	174.00	D018533	1.50	<0.005		0.001
			174.00	175.50	D018534	1.50	<0.005		0.001
			175.50	177.00	D018535	1.50	<0.005		0.001
			177.00	178.50	D018536	1.50	0.013		0.013
			178.50	180.00	D018538	1.50	<0.005		0.001
			180.00	181.50	D018539	1.50	0.008		0.008
			181.50	183.00	D018540	1.50	0.117		0.117
			183.00	184.50	D018541	1.50	0.337		0.337
			184.50	186.00	D018543	1.50	0.044		0.044
			186.00	187.50	D018544	1.50	0.036		0.036
			187.50	189.00	D018545	1.50	0.022		0.022
			189.00	190.50	D018546	1.50	0.016		0.016
			190.50	192.00	D018548	1.50	0.058		0.058
			192.00	193.10	D018549	1.10	<0.005		0.001
193.10	196.90	SY; FIN; POR	193.10	194.50	D018550	1.40	9.770		9.770
		<b>Syénite 50°; Grains fins; Porphyrique</b>	194.50	196.00	D018551	1.50	1.735		1.735
		Syénite à grains fins et porphyrique avec phénocristaux Xmm à Xcm..	196.00	196.90	D018552	0.90	0.042		0.042
196.90	237.70	GA; FIN; MTY	196.90	198.50	D018553	1.60	0.058		0.058
		<b>Gabbro 45°; Grains fins; Grains moyens</b>	198.50	200.00	D018554	1.50	<0.005		0.001
		Gabbro à grains fins à moyens, cisaillé au contact supér avec syénite.	200.00	201.50	D018555	1.50	<0.005		0.001
			201.50	203.00	D018556	1.50	<0.005		0.001
			203.00	204.50	D018558	1.50	<0.005		0.001
			204.50	206.00	D018559	1.50	<0.005		0.001
			206.00	207.50	D018560	1.50	<0.005		0.001
			207.50	209.00	D018561	1.50	<0.005		0.001
			209.00	210.50	D018562	1.50	<0.005		0.001
			210.50	212.00	D018563	1.50	0.012		0.012
			212.00	213.50	D018564	1.50	<0.005		0.001
			213.50	215.00	D018565	1.50	<0.005		0.001
			215.00	216.50	D018566	1.50	<0.005		0.001
			216.50	218.00	D018568	1.50	<0.005		0.001
			218.00	219.50	D018569	1.50	<0.005		0.001
			219.50	221.00	D018570	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			221.00	222.50	D018571	1.50	<0.005		0.001	
			222.50	224.00	D018572	1.50	<0.005		0.001	
			224.00	225.50	D018573	1.50	<0.005		0.001	
			225.50	227.00	D018574	1.50	<0.005		0.001	
			227.00	228.50	D018575	1.50	<0.005		0.001	
			228.50	230.00	D018576	1.50	<0.005		0.001	
			230.00	231.50	D018578	1.50	0.005		0.005	
			231.50	233.00	D018579	1.50	<0.005		0.001	
			233.00	234.50	D018580	1.50	<0.005		0.001	
			234.50	236.00	D018581	1.50	<0.005		0.001	
			236.00	237.70	D018583	1.70	<0.005		0.001	
237.70	239.40	QZVN <b>Veine de Quartz massive 15°</b> Veine de quartz massive avec l'inclusion de carbonate.	237.70	239.40	D018584	1.70	<0.005		0.001	
239.40	260.00	GW; MAS; FIN <b>Grauwacke 55°; Roche massive; Grains fins</b> Grauwacke massive, grains fins.	239.40	241.00	D018585	1.60	<0.005		0.001	
			241.00	242.50	D018586	1.50	0.005		0.005	
			242.50	244.00	D018588	1.50	0.008		0.008	
			244.00	245.50	D018589	1.50	0.028		0.028	
			245.50	247.00	D018590	1.50	0.005		0.005	
			247.00	248.50	D018591	1.50	0.029		0.029	
			248.50	250.00	D018592	1.50	0.578		0.578	
			250.00	251.50	D018593	1.50	0.007		0.007	
			251.50	253.00	D018594	1.50	0.384		0.384	
			253.00	254.50	D018595	1.50	0.006		0.006	
			254.50	256.00	D018596	1.50	0.005		0.005	
			256.00	257.50	D018598	1.50	0.005		0.005	
			257.50	259.00	D018599	1.50	0.005		0.005	
			259.00	260.00	D018600	1.00	0.026		0.026	
260.00	Fin du sondage Nombre d'échantillons : 157 Nombre d'échantillons QAQC : 23 Longueur totale échantillonnée : 233.40									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
26.60	28.00	D018422	M1	1.40	<0.005	0.001
32.50	34.00	D018427	J	1.50	0.722	0.722
46.00	47.50	D018437	D018436	1.50	<0.005	0.001
59.50	61.00	D018447	K	1.50	0.997	0.997
73.00	74.00	D018457	D018456	1.00	<0.005	0.001
76.50	79.50	D018462	M1	3.00	<0.005	0.001
84.30	85.50	D018467	L	1.20	1.750	1.750
97.50	99.00	D018477	D018476	1.50	<0.005	0.001
111.00	112.50	D018487	M	1.50	3.210	3.210
124.50	126.00	D018497	D018496	1.50	<0.005	0.001
130.50	132.00	D018502	M1	1.50	<0.005	0.001
136.50	138.00	D018507	J	1.50	0.755	0.755
150.00	151.50	D018517	D018516	1.50	<0.005	0.001
163.50	165.00	D018527	K	1.50	1.155	1.155
177.00	178.50	D018537	D018536	1.50	0.014	0.014
183.00	184.50	D018542	M1	1.50	<0.005	0.001
189.00	190.50	D018547	L	1.50	1.825	1.825
201.50	203.00	D018557	D018556	1.50	<0.005	0.001
215.00	216.50	D018567	M	1.50	3.010	3.010
228.50	230.00	D018577	D018576	1.50	<0.005	0.001
230.00	234.50	D018582	M1	4.50	<0.005	0.001
242.50	244.00	D018587	J	1.50	0.716	0.716
254.50	256.00	D018597	D018596	1.50	0.028	0.028

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-228**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    Guy Gbaguidi

Lot :

Du :                              2010-05-12

Date de description :

Au :                              2010-05-15

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                    347.00 m

Est	629 900.0
Nord	5 374 349.4
Élévation	280.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	318.90°	-59.00°	Oui
Reflex	8.00	346.50°	-58.90°	Oui
Reflex	11.00	3.40°	-58.70°	Oui
Reflex	14.00	336.50°	-59.10°	Oui
Reflex	17.00	6.80°	-60.00°	Oui
Reflex	20.00	337.80°	-59.60°	Oui
Reflex	23.00	28.90°	-59.90°	Oui
Reflex	26.00	357.40°	-59.40°	Non
Reflex	29.00	359.00°	-59.60°	Non
Reflex	32.00	359.20°	-59.70°	Non
Reflex	35.00	0.20°	-59.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.30°	-60.10°	Non
Reflex	41.00	359.60°	-59.50°	Non
Reflex	44.00	359.80°	-59.40°	Non
Reflex	47.00	359.70°	-59.50°	Non
Reflex	50.00	359.80°	-59.50°	Non
Reflex	53.00	359.90°	-59.50°	Non
Reflex	56.00	359.80°	-59.50°	Non
Reflex	59.00	359.90°	-59.40°	Non
Reflex	62.00	0.00°	-59.60°	Non
Reflex	65.00	359.80°	-59.30°	Non
Reflex	68.00	0.10°	-59.60°	Non
Reflex	71.00	0.10°	-59.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.10°	-59.60°	Non
Reflex	77.00	0.00°	-59.70°	Non
Reflex	80.00	359.50°	-58.70°	Non
Reflex	83.00	0.10°	-59.70°	Non
Reflex	86.00	0.00°	-59.70°	Non
Reflex	89.00	0.00°	-59.80°	Non
Reflex	92.00	359.90°	-59.80°	Non
Reflex	95.00	359.80°	-59.80°	Non
Reflex	98.00	0.30°	-60.20°	Non
Reflex	101.00	0.00°	-59.70°	Non
Reflex	104.00	0.20°	-59.60°	Non
Reflex	107.00	0.20°	-59.60°	Non
Reflex	110.00	0.30°	-59.60°	Non
Reflex	113.00	0.40°	-59.70°	Non
Reflex	116.00	0.30°	-59.70°	Non
Reflex	119.00	0.30°	-59.70°	Non
Reflex	122.00	0.20°	-59.70°	Non
Reflex	125.00	0.20°	-59.70°	Non
Reflex	128.00	0.20°	-59.60°	Non
Reflex	131.00	0.20°	-59.70°	Non
Reflex	134.00	0.40°	-59.60°	Non
Reflex	137.00	0.30°	-59.60°	Non
Reflex	140.00	0.30°	-59.60°	Non
Reflex	143.00	0.50°	-59.60°	Non
Reflex	146.00	0.70°	-59.60°	Non
Reflex	149.00	0.70°	-59.60°	Non
Reflex	152.00	0.90°	-59.60°	Non
Reflex	155.00	1.00°	-59.60°	Non
Reflex	158.00	1.20°	-59.70°	Non
Reflex	161.00	1.20°	-59.70°	Non
Reflex	164.00	1.30°	-59.60°	Non
Reflex	167.00	1.30°	-59.50°	Non
Reflex	170.00	1.40°	-59.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	1.50°	-59.50°	Non
Reflex	176.00	1.50°	-59.50°	Non
Reflex	179.00	1.60°	-59.50°	Non
Reflex	182.00	1.70°	-59.40°	Non
Reflex	185.00	1.90°	-59.60°	Non
Reflex	188.00	2.00°	-59.50°	Non
Reflex	191.00	2.10°	-59.50°	Non
Reflex	194.00	2.10°	-59.40°	Non
Reflex	197.00	2.20°	-59.40°	Non
Reflex	200.00	1.90°	-59.50°	Non
Reflex	203.00	2.40°	-59.50°	Non
Reflex	206.00	2.50°	-59.50°	Non
Reflex	209.00	2.70°	-59.50°	Non
Reflex	212.00	2.80°	-59.50°	Non
Reflex	215.00	3.00°	-59.40°	Non
Reflex	218.00	3.30°	-59.40°	Non
Reflex	221.00	3.40°	-59.30°	Non
Reflex	224.00	3.50°	-59.30°	Non
Reflex	227.00	3.70°	-59.30°	Non
Reflex	230.00	3.90°	-59.40°	Non
Reflex	233.00	4.00°	-59.40°	Non
Reflex	236.00	4.20°	-59.40°	Non
Reflex	239.00	4.30°	-59.50°	Non
Reflex	242.00	4.60°	-59.50°	Non
Reflex	245.00	4.70°	-59.60°	Non
Reflex	248.00	4.90°	-59.50°	Non
Reflex	251.00	4.90°	-59.50°	Non
Reflex	254.00	5.00°	-59.50°	Non
Reflex	257.00	5.10°	-59.40°	Non
Reflex	260.00	5.40°	-59.40°	Non
Reflex	263.00	5.30°	-59.30°	Non
Reflex	266.00	5.50°	-59.30°	Non
Reflex	269.00	5.60°	-59.40°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.80°	-59.30°	Non					
Reflex	275.00	6.00°	-59.30°	Non					
Reflex	278.00	6.00°	-59.30°	Non					
Reflex	281.00	6.10°	-59.20°	Non					
Reflex	284.00	6.20°	-59.20°	Non					
Reflex	287.00	6.30°	-59.20°	Non					
Reflex	290.00	6.30°	-59.30°	Non					
Reflex	293.00	6.40°	-59.30°	Non					
Reflex	296.00	6.40°	-59.30°	Non					
Reflex	299.00	6.60°	-59.30°	Non					
Reflex	302.00	6.70°	-59.30°	Non					
Reflex	305.00	6.70°	-59.30°	Non					
Reflex	308.00	6.80°	-59.30°	Non					
Reflex	311.00	7.00°	-59.20°	Non					
Reflex	314.00	7.10°	-59.00°	Non					
Reflex	317.00	7.20°	-59.00°	Non					
Reflex	320.00	7.60°	-58.90°	Non					
Reflex	323.00	7.80°	-59.00°	Non					
Reflex	326.00	7.80°	-58.90°	Non					
Reflex	329.00	7.90°	-59.00°	Non					
Reflex	332.00	8.10°	-59.00°	Non					
Reflex	335.00	8.30°	-59.00°	Non					
Reflex	338.00	8.60°	-59.10°	Non					
Reflex	341.00	8.80°	-59.00°	Non					
Reflex	344.00	9.00°	-59.00°	Non					
Reflex	347.00	9.10°	-59.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	25.60	MT							
		<b>Mort-terrain</b>							
25.60	69.00	SY; POR	25.60	27.00	D023741	1.40	0.452	0.452	
		<b>Syénite 25°; Porphyrique</b>	27.00	28.50	D023742	1.50	2.430	2.430	
		Syénite porphyrique silicifiée, fortement carbonatée, silicifiée et remplacée par endroit.	28.50	30.00	D023743	1.50	0.037	0.037	
			30.00	31.50	D023744	1.50	0.042	0.042	
			31.50	33.00	D023746	1.50	0.695	0.695	
			33.00	34.50	D023747	1.50	0.066	0.066	
			34.50	36.00	D023748	1.50	0.918	0.918	
			36.00	37.50	D023749	1.50	0.791	0.791	
			37.50	39.00	D023750	1.50	1.505	1.505	
			39.00	40.50	D023751	1.50	1.025	1.025	
			40.50	42.00	D023752	1.50	0.399	0.399	
			42.00	43.50	D023753	1.50	1.235	1.235	
			43.50	45.00	D023754	1.50	0.748	0.748	
			45.00	46.50	D023756	1.50	3.330	3.330	
			46.50	48.00	D023757	1.50	4.750	4.750	
			48.00	49.50	D023758	1.50	1.395	1.395	
			49.50	51.00	D023759	1.50	6.290	6.290	
			51.00	52.50	D023761	1.50	8.450	8.450	
			52.50	54.00	D023762	1.50	5.270	5.270	
			54.00	55.50	D023763	1.50	1.955	1.955	
			55.50	57.00	D023764	1.50	3.100	3.100	
			57.00	58.50	D023766	1.50	1.255	1.255	
			58.50	60.00	D023767	1.50	>10.0	18.35	18.350
			60.00	61.50	D023768	1.50	>10.0	13.55	13.550
			61.50	63.00	D023769	1.50	8.480		8.480
			63.00	64.50	D023770	1.50	4.310		4.310
			64.50	66.00	D023771	1.50	5.170		5.170
			66.00	67.50	D023772	1.50	9.700		9.700
			67.50	69.00	D023773	1.50	0.627		0.627
69.00	272.60	BA; AMY	69.00	70.50	D023774	1.50	0.012		0.012
		<b>Basalte 20°; Amygdalaire</b>	70.50	72.00	D023776	1.50	<0.005		0.001
		Fortement carbonaté.							

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	72.00	73.50	D023777	1.50	0.010		0.010
	73.50	75.00	D023778	1.50	0.007		0.007
	75.00	76.50	D023779	1.50	<0.005		0.001
	76.50	78.00	D023780	1.50	0.005		0.005
	78.00	79.50	D023781	1.50	0.008		0.008
	79.50	81.00	D023782	1.50	<0.005		0.001
	81.00	82.50	D023783	1.50	<0.005		0.001
	82.50	84.00	D023784	1.50	<0.005		0.001
	84.00	85.50	D023786	1.50	<0.005		0.001
	85.50	87.00	D023787	1.50	0.012		0.012
	87.00	88.40	D023788	1.40	0.010		0.010
	88.40	90.00	D023789	1.60	0.008		0.008
	90.00	91.50	D023790	1.50	<0.005		0.001
	91.50	93.00	D023791	1.50	<0.005		0.001
	93.00	94.50	D023792	1.50	<0.005		0.001
	94.50	96.00	D023793	1.50	<0.005		0.001
	96.00	97.50	D023794	1.50	<0.005		0.001
	97.50	99.00	D023796	1.50	<0.005		0.001
	99.00	100.50	D023797	1.50	<0.005		0.001
	100.50	102.00	D023798	1.50	0.008		0.008
	102.00	103.50	D023799	1.50	<0.005		0.001
	103.50	105.00	D023801	1.50	<0.005		0.001
	105.00	106.50	D023802	1.50	<0.005		0.001
	106.50	108.00	D023803	1.50	<0.005		0.001
	108.00	109.50	D023804	1.50	<0.005		0.001
	109.50	111.00	D023806	1.50	<0.005		0.001
	111.00	112.50	D023807	1.50	<0.005		0.001
	112.50	114.00	D023808	1.50	<0.005		0.001
	114.00	115.50	D023809	1.50	0.007		0.007
	115.50	117.00	D023810	1.50	<0.005		0.001
	117.00	118.50	D023811	1.50	0.012		0.012
	118.50	120.00	D023812	1.50	<0.005		0.001
	120.00	121.50	D023813	1.50	0.008		0.008



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	121.50	123.00	D023814	1.50	<0.005		0.001
	123.00	124.50	D023816	1.50	<0.005		0.001
	124.50	126.00	D023817	1.50	<0.005		0.001
	126.00	127.50	D023818	1.50	<0.005		0.001
	127.50	129.00	D023819	1.50	<0.005		0.001
	129.00	130.50	D023820	1.50	<0.005		0.001
	130.50	132.00	D023821	1.50	<0.005		0.001
	132.00	133.50	D023822	1.50	<0.005		0.001
	133.50	135.00	D023823	1.50	<0.005		0.001
	135.00	136.50	D023824	1.50	<0.005		0.001
	136.50	138.00	D023826	1.50	<0.005		0.001
	138.00	139.50	D023827	1.50	<0.005		0.001
	139.50	141.00	D023828	1.50	<0.005		0.001
	141.00	142.50	D023829	1.50	<0.005		0.001
	142.50	144.00	D023830	1.50	<0.005		0.001
	144.00	145.50	D023831	1.50	<0.005		0.001
	145.50	147.00	D023832	1.50	<0.005		0.001
	147.00	148.50	D023833	1.50	<0.005		0.001
	148.50	150.00	D023834	1.50	<0.005		0.001
	150.00	151.50	D023836	1.50	0.006		0.006
	151.50	153.00	D023837	1.50	<0.005		0.001
	153.00	154.50	D023838	1.50	<0.005		0.001
	154.50	156.00	D023839	1.50	<0.005		0.001
	156.00	157.50	D023841	1.50	<0.005		0.001
	157.50	159.00	D023842	1.50	<0.005		0.001
	159.00	160.50	D023843	1.50	<0.005		0.001
	160.50	162.00	D023844	1.50	<0.005		0.001
	162.00	163.50	D023846	1.50	<0.005		0.001
	163.50	165.00	D023847	1.50	<0.005		0.001
	165.00	166.50	D023848	1.50	<0.005		0.001
	166.50	168.00	D023849	1.50	<0.005		0.001
	168.00	169.50	D023850	1.50	<0.005		0.001
	169.50	171.00	D023851	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	171.00	172.50	D023852	1.50	<0.005		0.001
	172.50	174.00	D023853	1.50	<0.005		0.001
	174.00	175.50	D023854	1.50	<0.005		0.001
	175.50	177.00	D023856	1.50	<0.005		0.001
	177.00	178.50	D023857	1.50	<0.005		0.001
	178.50	180.00	D023858	1.50	<0.005		0.001
	180.00	181.50	D023859	1.50	<0.005		0.001
	181.50	183.00	D023860	1.50	<0.005		0.001
	183.00	184.50	D023861	1.50	<0.005		0.001
	184.50	186.00	D023862	1.50	<0.005		0.001
	186.00	187.30	D023863	1.30	<0.005		0.001
	187.30	189.00	D023864	1.70	<0.005		0.001
	189.00	190.50	D023866	1.50	<0.005		0.001
	190.50	192.00	D023867	1.50	<0.005		0.001
	192.00	193.60	D023868	1.60	<0.005		0.001
	193.60	195.00	D023869	1.40	<0.005		0.001
	195.00	196.50	D023870	1.50	<0.005		0.001
	196.50	198.00	D023871	1.50	<0.005		0.001
	198.00	199.50	D023872	1.50	<0.005		0.001
	199.50	201.00	D023873	1.50	<0.005		0.001
	201.00	202.50	D023874	1.50	<0.005		0.001
	202.50	204.00	D023876	1.50	<0.005		0.001
	204.00	205.50	D023877	1.50	<0.005		0.001
	205.50	207.00	D023878	1.50	<0.005		0.001
	207.00	208.50	D023879	1.50	<0.005		0.001
	208.50	210.00	D023881	1.50	<0.005		0.001
	210.00	211.50	D023882	1.50	<0.005		0.001
	211.50	213.00	D023883	1.50	<0.005		0.001
	213.00	214.50	D023884	1.50	<0.005		0.001
	214.50	216.00	D023886	1.50	<0.005		0.001
	216.00	217.50	D023887	1.50	<0.005		0.001
	217.50	219.00	D023888	1.50	<0.005		0.001
	219.00	220.50	D023889	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	220.50	222.00	D023890	1.50	<0.005		0.001
	222.00	223.50	D023891	1.50	<0.005		0.001
	223.50	225.00	D023892	1.50	<0.005		0.001
	225.00	226.50	D023893	1.50	<0.005		0.001
	226.50	228.00	D023894	1.50	<0.005		0.001
	228.00	229.50	D023896	1.50	<0.005		0.001
	229.50	231.00	D023897	1.50	<0.005		0.001
	231.00	232.50	D023898	1.50	<0.005		0.001
	232.50	234.00	D023899	1.50	<0.005		0.001
	234.00	235.50	D023900	1.50	<0.005		0.001
	235.50	237.00	D023901	1.50	<0.005		0.001
	237.00	238.50	D023902	1.50	<0.005		0.001
	238.50	240.00	D023903	1.50	<0.005		0.001
	240.00	241.50	D023904	1.50	<0.005		0.001
	241.50	243.00	D023906	1.50	<0.005		0.001
	243.00	244.50	D023907	1.50	<0.005		0.001
	244.50	246.00	D023908	1.50	<0.005		0.001
	246.00	247.50	D023909	1.50	<0.005		0.001
	247.50	249.00	D023910	1.50	<0.005		0.001
	249.00	250.50	D023911	1.50	<0.005		0.001
	250.50	252.00	D023912	1.50	0.005		0.005
	252.00	253.00	D023913	1.00	0.008		0.008
	253.00	254.30	D023914	1.30	<0.005		0.001
	254.30	256.00	D023916	1.70	<0.005		0.001
	256.00	257.50	D023917	1.50	<0.005		0.001
	257.50	259.00	D023918	1.50	<0.005		0.001
	259.00	260.50	D023919	1.50	<0.005		0.001
	260.50	262.00	D023921	1.50	<0.005		0.001
	262.00	263.50	D023922	1.50	0.007		0.007
	263.50	265.00	D023923	1.50	0.008		0.008
	265.00	266.50	D023924	1.50	<0.005		0.001
	266.50	268.00	D023926	1.50	<0.005		0.001
	268.00	269.50	D023927	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
272.60	310.00	GA <b>Gabbro</b> gabbro micro-grenu, massive, fortement carbonaté.	269.50	271.00	D023928	1.50	<0.005		0.001
			271.00	272.60	D023929	1.60	<0.005		0.001
			272.60	274.00	D023930	1.40	<0.005		0.001
			274.00	275.50	D023931	1.50	<0.005		0.001
			275.50	277.00	D023932	1.50	<0.005		0.001
			277.00	278.50	D023933	1.50	<0.005		0.001
			278.50	280.00	D023934	1.50	<0.005		0.001
			280.00	281.50	D023936	1.50	<0.005		0.001
			281.50	283.00	D023937	1.50	0.005		0.005
			283.00	284.50	D023938	1.50	<0.005		0.001
			284.50	286.00	D023939	1.50	<0.005		0.001
			286.00	287.50	D023940	1.50	<0.005		0.001
			287.50	289.00	D023941	1.50	<0.005		0.001
			289.00	290.50	D023942	1.50	<0.005		0.001
			290.50	292.00	D023943	1.50	<0.005		0.001
			292.00	293.50	D023944	1.50	<0.005		0.001
			293.50	295.00	D023946	1.50	<0.005		0.001
			295.00	296.50	D023947	1.50	<0.005		0.001
			296.50	298.00	D023948	1.50	<0.005		0.001
			298.00	299.50	D023949	1.50	<0.005		0.001
310.00	347.00	BA; AMY <b>Basalte; Amygdalaire</b> Basalte amygdalaire fortement carbonaté	299.50	301.00	D023950	1.50	<0.005		0.001
			301.00	302.50	D023951	1.50	<0.005		0.001
			302.50	304.00	D023952	1.50	<0.005		0.001
			304.00	305.50	D023953	1.50	<0.005		0.001
			305.50	307.00	D023954	1.50	<0.005		0.001
			307.00	308.50	D023956	1.50	<0.005		0.001
			308.50	310.00	D023957	1.50	<0.005		0.001
			310.00	311.50	D023958	1.50	<0.005		0.001
			311.50	313.00	D023959	1.50	<0.005		0.001
			313.00	314.50	D023961	1.50	<0.005		0.001
314.50	316.00	D023962	1.50	<0.005		0.001			
316.00	317.50	D023963	1.50	<0.005		0.001			
317.50	319.00	D023964	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	319.00	320.50	D023966	1.50	<0.005		0.001
	320.50	322.00	D023967	1.50	<0.005		0.001
	322.00	323.00	D023968	1.00	<0.005		0.001
	323.00	324.00	D023969	1.00	<0.005		0.001
	324.00	325.50	D023970	1.50	<0.005		0.001
	325.50	327.00	D023971	1.50	<0.005		0.001
	327.00	328.50	D023972	1.50	<0.005		0.001
	328.50	330.00	D023973	1.50	<0.005		0.001
	330.00	331.50	D023974	1.50	<0.005		0.001
	331.50	333.00	D023976	1.50	<0.005		0.001
	333.00	334.50	D023977	1.50	<0.005		0.001
	334.50	336.00	D023978	1.50	<0.005		0.001
	336.00	337.50	D023979	1.50	<0.005		0.001
	337.50	339.00	D023980	1.50	<0.005		0.001
	339.00	340.50	D023981	1.50	<0.005		0.001
	340.50	342.00	D023982	1.50	<0.005		0.001
	342.00	343.50	D023983	1.50	<0.005		0.001
	343.50	345.00	D023984	1.50	<0.005		0.001
	345.00	346.00	D023986	1.00	<0.005		0.001
	346.00	347.00	D023987	1.00	0.014		0.014
347.00	Fin du sondage Nombre d'échantillons : 216 Nombre d'échantillons QAQC : 31 Longueur totale échantillonnée : 321.40						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
30.00	31.50	D023745	D023744	1.50	0.037	0.037
43.50	43.50	D023755	L	0.00	1.925	1.925
49.50	49.50	D023760	M1	0.00	<0.005	0.001
55.50	57.00	D023765	D023764	1.50	3.140	3.140
69.00	69.00	D023775	J	0.00	0.696	0.696
82.50	84.00	D023785	D023784	1.50	0.005	0.005
96.00	96.00	D023795	K	0.00	1.055	1.055
102.00	102.00	D023800	M1	0.00	<0.005	0.001
108.00	109.50	D023805	D023804	1.50	<0.005	0.001
121.50	121.50	D023815	L	0.00	1.925	1.925
135.00	136.50	D023825	D023824	1.50	<0.005	0.001
148.50	148.50	D023835	M	0.00	2.590	2.590
154.50	154.50	D023840	M1	0.00	<0.005	0.001
160.50	162.00	D023845	D023844	1.50	<0.005	0.001
174.00	174.00	D023855	J	0.00	0.782	0.782
187.30	188.60	D023865	D023864	1.30	<0.005	0.001
201.00	201.00	D023875	M	0.00	3.010	3.010
207.00	207.00	D023880	M1	0.00	<0.005	0.001
213.00	214.50	D023885	D023884	1.50	<0.005	0.001
226.50	226.50	D023895	J	0.00	0.771	0.771
240.00	241.50	D023905	D023904	1.50	<0.005	0.001
253.00	253.00	D023915	K	0.00	1.065	1.065
259.00	259.00	D023920	M1	0.00	<0.005	0.001
265.00	266.50	D023925	D023924	1.50	0.005	0.005
278.50	278.50	D023935	L	0.00	2.220	2.220
292.00	293.50	D023945	D023944	1.50	<0.005	0.001
305.50	305.50	D023955	M	0.00	2.890	2.890
311.50	311.50	D023960	M1	0.00	<0.005	0.001
317.50	319.00	D023965	D023964	1.50	<0.005	0.001
330.00	330.00	D023975	J	0.00	0.731	0.731
343.50	345.00	D023985	D023984	1.50	<0.005	0.001



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	83.00	184.60°	-70.40°	Non
Reflex	86.00	184.70°	-70.30°	Non
Reflex	89.00	184.10°	-70.20°	Non
Reflex	92.00	184.40°	-70.10°	Non
Reflex	95.00	184.00°	-70.10°	Non
Reflex	98.00	183.80°	-70.00°	Non
Reflex	101.00	184.00°	-69.80°	Non
Reflex	104.00	183.30°	-69.80°	Non
Reflex	107.00	182.70°	-69.70°	Non
Reflex	110.00	182.30°	-69.60°	Non
Reflex	113.00	182.00°	-69.40°	Non
Reflex	116.00	181.70°	-69.20°	Non
Reflex	119.00	181.60°	-69.10°	Non
Reflex	122.00	181.00°	-69.00°	Non
Reflex	125.00	180.50°	-68.90°	Non
Reflex	128.00	180.80°	-68.70°	Non
Reflex	131.00	180.70°	-68.60°	Non
Reflex	134.00	180.30°	-68.40°	Non
Reflex	137.00	180.30°	-68.30°	Non
Reflex	140.00	179.90°	-68.20°	Non
Reflex	143.00	179.80°	-68.00°	Non
Reflex	146.00	179.70°	-67.70°	Non
Reflex	149.00	180.00°	-67.60°	Non
Reflex	152.00	179.70°	-67.50°	Non
Reflex	155.00	178.50°	-67.40°	Non
Reflex	158.00	179.50°	-67.20°	Non
Reflex	161.00	179.20°	-67.00°	Non
Reflex	164.00	179.30°	-66.80°	Non
Reflex	167.00	178.80°	-66.60°	Non
Reflex	170.00	178.50°	-66.30°	Non
Reflex	173.00	178.40°	-66.10°	Non
Reflex	176.00	178.00°	-65.80°	Non
Reflex	179.00	178.10°	-65.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	182.00	177.60°	-65.30°	Non
Reflex	185.00	177.20°	-64.80°	Non
Reflex	188.00	176.80°	-64.30°	Non
Reflex	191.00	176.00°	-63.90°	Non
Reflex	194.00	175.90°	-63.40°	Non
Reflex	197.00	175.40°	-62.80°	Non
Reflex	200.00	174.70°	-62.10°	Non
Reflex	203.00	174.50°	-61.30°	Non
Reflex	206.00	174.70°	-60.60°	Non
Reflex	209.00	174.30°	-59.90°	Non
Reflex	212.00	174.30°	-59.00°	Non
Reflex	215.00	174.00°	-58.10°	Non
Reflex	218.00	174.00°	-57.90°	Non
Reflex	221.00	174.10°	-57.90°	Non
Reflex	224.00	174.00°	-57.80°	Non
Reflex	227.00	174.00°	-57.70°	Non
Reflex	230.00	173.80°	-57.60°	Non
Reflex	233.00	173.90°	-57.60°	Non
Reflex	236.00	174.10°	-57.50°	Non
Reflex	239.00	173.90°	-57.40°	Non
Reflex	242.00	174.00°	-57.30°	Non
Reflex	245.00	173.60°	-57.30°	Non
Reflex	248.00	173.40°	-57.10°	Non
Reflex	251.00	173.30°	-57.10°	Non
Reflex	254.00	173.10°	-57.00°	Non
Reflex	257.00	173.10°	-56.90°	Non
Reflex	260.00	173.20°	-56.90°	Non
Reflex	263.00	173.20°	-57.00°	Non
Reflex	266.00	173.50°	-57.10°	Non
Reflex	269.00	174.00°	-56.90°	Non
Reflex	272.00	173.40°	-56.70°	Non
Reflex	275.00	173.30°	-56.60°	Non
Reflex	278.00	173.30°	-56.60°	Non



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	281.00	173.00°	-56.50°	Non					
Reflex	284.00	173.30°	-56.30°	Non					
Reflex	287.00	174.80°	-56.10°	Non					
Reflex	290.00	174.70°	-56.00°	Non					
Reflex	293.00	174.70°	-55.90°	Non					
Reflex	296.00	174.70°	-55.90°	Non					
Reflex	299.00	174.50°	-55.90°	Non					
Reflex	302.00	175.30°	-56.00°	Non					
Reflex	305.00	174.50°	-55.90°	Non					
Reflex	308.00	174.40°	-55.90°	Non					
Reflex	311.00	174.50°	-56.00°	Non					
Reflex	314.00	174.70°	-55.90°	Non					
Reflex	317.00	174.50°	-55.80°	Non					
Reflex	320.00	174.60°	-55.70°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	36.00	MT <b>Mort-terrain</b> No recovery.						
36.00	70.00	TU <b>Tuf à cendre/lapillis 45°</b> Tuf à granulo très fine. Couleur gris à gris sombre. Présence de litage qui est un plan de cassure et de remplissage (quartz carbonate) privilégié: 50'. Présence de graphite par endroit. Altération carbonatée. Non magnétique.						
36.00	72.40	CB <b>Carbonaté</b>	36.00	37.50	D031548	1.50	<0.005	0.001
			37.50	39.00	D031549	1.50	0.011	0.011
			39.00	40.50	D031550	1.50	<0.005	0.001
			40.50	42.00	D031551	1.50	<0.005	0.001
			42.00	43.50	D031552	1.50	<0.005	0.001
			43.50	45.00	D031554	1.50	<0.005	0.001
			45.00	46.50	D031555	1.50	0.005	0.005
			46.50	48.00	D031556	1.50	<0.005	0.001
			48.00	49.50	D031557	1.50	0.005	0.005
			49.50	51.00	D031558	1.50	<0.005	0.001
			51.00	52.50	D031559	1.50	<0.005	0.001
			52.50	54.00	D031560	1.50	0.006	0.006
			54.00	55.50	D031561	1.50	<0.005	0.001
			55.50	57.00	D031562	1.50	<0.005	0.001
			57.00	58.50	D031564	1.50	<0.005	0.001
			58.50	60.00	D031565	1.50	<0.005	0.001
			60.00	61.50	D031566	1.50	<0.005	0.001
			61.50	63.00	D031567	1.50	<0.005	0.001
61.60	61.62	FAI <b>Faille 40°</b> Faille avec remplissage de boue (fault gouge).	63.00	64.50	D031568	1.50	<0.005	0.001
			64.50	66.00	D031569	1.50	<0.005	0.001
			66.00	67.50	D031571	1.50	<0.005	0.001
			67.50	69.00	D031572	1.50	<0.005	0.001
			69.00	70.00	D031574	1.00	0.014	0.014

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
69.80	72.30	FRC <b>Fracturé</b> Zone broyée et très lessivée (pas de pyrite visible). Altération chloritique.							
70.00	71.00	NR <b>Carotte perdue</b> No recovery.							
71.00	118.80	TU <b>Tuf à cendre/lapillis</b> Tuf à granulo très fine. Couleur gris à gris sombre. Présence de litage qui est un plan de cassure et de remplissage (quartz carbonate) privilégié: 50'. Présence de graphite par endroit. Altération carbonatée et silicifiée en début d'échantillon. Non magnétique.	71.00	72.30	D031575	1.30	0.099		0.099
			72.30	74.00	D031576	1.70	0.927		0.927
72.40	82.20	SI <b>Silicifié</b> Silicifié avec des passages décimétriques hématésés et carbonatées.	74.00	75.50	D031577	1.50	0.896		0.896
			75.50	77.00	D031578	1.50	0.828		0.828
			77.00	78.50	D031579	1.50	2.800		2.800
			78.50	80.00	D031580	1.50	0.015		0.015
			80.00	81.50	D031581	1.50	2.120		2.120
82.20	86.80	CB <b>Carbonaté</b>	81.50	83.00	D031582	1.50	1.280		1.280
			83.00	84.50	D031584	1.50	0.455		0.455
			84.50	86.00	D031585	1.50	<0.005		0.001
			86.00	86.80	D031586	0.80	<0.005		0.001
			86.80	88.50	D031587	1.70	<0.005		0.001
			88.50	90.00	D031588	1.50	<0.005		0.001
			90.00	91.50	D031589	1.50	<0.005		0.001
			91.50	93.00	D031590	1.50	<0.005		0.001
			93.00	94.50	D031591	1.50	<0.005		0.001
			94.50	96.00	D031592	1.50	<0.005		0.001
			96.00	97.50	D031594	1.50	0.005		0.005
			97.50	99.00	D031595	1.50	<0.005		0.001
			99.00	100.50	D031596	1.50	<0.005		0.001
100.50	102.00	D031597	1.50	<0.005		0.001			
102.00	103.50	D031598	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			103.50	105.00	D031599	1.50	<0.005	0.001
			105.00	106.50	D031600	1.50	<0.005	0.001
			106.50	108.00	D031601	1.50	<0.005	0.001
			108.00	109.50	D031602	1.50	<0.005	0.001
			109.50	111.00	D031604	1.50	<0.005	0.001
			111.00	112.50	D031605	1.50	<0.005	0.001
			112.50	114.00	D031606	1.50	<0.005	0.001
			114.00	115.50	D031607	1.50	<0.005	0.001
			115.50	117.10	D031608	1.60	<0.005	0.001
			117.10	118.80	D031609	1.70	<0.005	0.001
118.80	119.00	NR	118.80	120.50	D031611	1.70	<0.005	0.001
		<b>Carotte perdue</b>						
119.00	132.50	TU	120.50	122.00	D031612	1.50	<0.005	0.001
		<b>Tuf à cendre/lapillis</b>	122.00	123.50	D031614	1.50	<0.005	0.001
		Tuf à granulo très fine.	123.50	125.00	D031615	1.50	<0.005	0.001
		Couleur gris à gris sombre.	125.00	126.50	D031616	1.50	<0.005	0.001
		Présence de litage qui est un plan de cassure et de remplissage (quartz carbonate) privilégié: 50'.	126.50	128.00	D031617	1.50	<0.005	0.001
		Présence de graphite par endroit.	128.00	129.50	D031618	1.50	<0.005	0.001
		Altération inconnue (chloritisation?).	129.50	131.00	D031619	1.50	<0.005	0.001
		Non magnétique.	131.00	132.50	D031620	1.50	<0.005	0.001
132.50	162.00	GR	132.50	134.00	D031621	1.50	<0.005	0.001
		<b>Grès</b>	134.00	135.50	D031622	1.50	<0.005	0.001
		Métasédiment de granularité fine à moyenne.	135.50	137.00	D031624	1.50	<0.005	0.001
		Altération chloritique.	137.00	138.50	D031625	1.50	0.006	0.006
			138.50	140.00	D031626	1.50	<0.005	0.001
			140.00	141.50	D031627	1.50	0.020	0.020
			141.50	143.00	D031628	1.50	<0.005	0.001
			143.00	144.50	D031629	1.50	<0.005	0.001
			144.50	146.00	D031630	1.50	<0.005	0.001
			146.00	147.70	D031631	1.70	<0.005	0.001
			147.70	148.60	D031632	0.90	0.007	0.007
148.60	161.00	GR	148.60	150.00	D031634	1.40	<0.005	0.001
		<b>Grès</b>	150.00	151.50	D031635	1.50	<0.005	0.001
		Grès moyen à grossier.						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
162.00	181.00	MS <b>Mudstone</b> Mudstone. Couleur gris pale. Peu d'intrusion. Altération chlorite.	151.50	153.00	D031636	1.50	<0.005		0.001
			153.00	154.50	D031637	1.50	<0.005		0.001
			154.50	156.00	D031638	1.50	<0.005		0.001
			156.00	157.50	D031639	1.50	<0.005		0.001
			157.50	159.00	D031640	1.50	<0.005		0.001
			159.00	160.50	D031641	1.50	<0.005		0.001
			160.50	162.00	D031642	1.50	0.005		0.005
			162.00	163.50	D031644	1.50	<0.005		0.001
			163.50	165.00	D031645	1.50	<0.005		0.001
			165.00	166.50	D031646	1.50	<0.005		0.001
			166.50	168.00	D031647	1.50	<0.005		0.001
			168.00	169.50	D031648	1.50	0.005		0.005
			169.50	171.00	D031649	1.50	0.005		0.005
			171.00	171.90	D031651	0.90	0.005		0.005
			171.90	173.50	D031652	1.60	<0.005		0.001
			173.50	175.20	D031654	1.70	<0.005		0.001
			175.20	176.50	D031655	1.30	<0.005		0.001
			176.50	178.00	D031656	1.50	<0.005		0.001
178.00	179.50	D031657	1.50	<0.005		0.001			
179.50	181.00	D031658	1.50	<0.005		0.001			
179.60	181.00	FRC <b>Fracturé 20°</b> Zone fracturée marquant la limite entre le sédiment non carbonaté supérieur et le sédiment carbonaté inférieur. Les fractures vont de 0° à 45°.							
181.00	215.50	GR <b>Grès</b> Grès de granulométrie moyenne. Couleur gris pale. Présence de nombreux clastes: feldspaths ankéritisés jaunâtre, sédiment allochtone. Unité peu minéralisé en pyrite. Elle se retrouve dans les parties à granulo plus fine et dans les veines de Qtz carbonate.	181.00	182.50	D031659	1.50	<0.005		0.001
			182.50	184.00	D031660	1.50	<0.005		0.001
			184.00	185.50	D031661	1.50	0.006		0.006
			185.50	187.00	D031662	1.50	<0.005		0.001
			187.00	188.50	D031664	1.50	<0.005		0.001
			188.50	190.00	D031665	1.50	<0.005		0.001
			190.00	191.50	D031666	1.50	<0.005		0.001
			191.50	193.00	D031667	1.50	<0.005		0.001
			193.00	194.50	D031668	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			194.50	196.00	D031669	1.50	<0.005		0.001
			196.00	197.50	D031670	1.50	<0.005		0.001
			197.50	199.00	D031671	1.50	<0.005		0.001
			199.00	200.50	D031672	1.50	<0.005		0.001
			200.50	202.00	D031674	1.50	<0.005		0.001
			202.00	203.50	D031675	1.50	<0.005		0.001
			203.50	205.00	D031676	1.50	<0.005		0.001
			205.00	206.50	D031677	1.50	<0.005		0.001
			206.50	208.00	D031678	1.50	<0.005		0.001
			208.00	209.50	D031679	1.50	<0.005		0.001
			209.50	211.00	D031680	1.50	<0.005		0.001
			211.00	212.50	D031681	1.50	<0.005		0.001
			212.50	214.00	D031682	1.50	0.089		0.089
			214.00	215.50	D031684	1.50	0.138		0.138
215.50	244.80	UM	215.50	217.00	D031685	1.50	0.453		0.453
		<b>Ultramafite serpentinisée</b>	217.00	218.50	D031686	1.50	0.835		0.835
		Ultramafite très fine, voire aphanitique.	218.50	220.00	D031687	1.50	0.375		0.375
		Minéralisation en pyrite disséminée bien développée.	220.00	221.10	D031688	1.10	0.421		0.421
		Carbonatée par endroit, sinon chloritisé, et talc carbonaté à la fin de l'unité.	221.10	222.50	D031689	1.40	0.414		0.414
			222.50	224.00	D031691	1.50	0.264		0.264
			224.00	225.50	D031692	1.50	0.131		0.131
			225.50	227.00	D031694	1.50	0.036		0.036
			227.00	228.50	D031695	1.50	0.038		0.038
			228.50	230.00	D031696	1.50	0.017		0.017
			230.00	231.50	D031697	1.50	0.015		0.015
			231.50	233.00	D031698	1.50	0.015		0.015
			233.00	234.40	D031699	1.40	0.024		0.024
			234.40	236.00	D031700	1.60	0.140		0.140
			236.00	237.50	D031701	1.50	0.027		0.027
			237.50	239.00	D031702	1.50	0.256		0.256
			239.00	240.50	D031704	1.50	0.146		0.146
			240.50	242.00	D031705	1.50	0.109		0.109
			242.00	243.50	D031706	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
244.80	245.00	NR <b>Carotte perdue</b> No recovery.	243.50	244.80	D031707	1.30	<0.005		0.001
245.00	267.10	UM <b>Ultramafite serpentinisée</b> Altération talc carbonate typique.	245.00	246.50	D031708	1.50	<0.005		0.001
			246.50	248.00	D031709	1.50	<0.005		0.001
			248.00	249.50	D031710	1.50	<0.005		0.001
			249.50	251.00	D031711	1.50	<0.005		0.001
			251.00	252.50	D031712	1.50	<0.005		0.001
			252.50	254.00	D031714	1.50	<0.005		0.001
			254.00	255.50	D031715	1.50	<0.005		0.001
			255.50	257.00	D031716	1.50	0.057		0.057
			257.00	258.50	D031717	1.50	0.031		0.031
			258.50	260.00	D031718	1.50	0.012		0.012
			260.00	261.50	D031719	1.50	<0.005		0.001
260.30	262.20	FAI <b>Faille 30°</b> Faille dans le sédiment. Altération talc carbonate bien développée.	261.50	263.00	D031720	1.50	<0.005		0.001
			263.00	264.20	D031721	1.20	<0.005		0.001
			264.20	265.50	D031722	1.30	<0.005		0.001
			265.50	267.10	D031724	1.60	<0.005		0.001
267.10	290.80	MS <b>Mudstone</b> Métasédiment de granulo fine. Altération chloritique. Contient un litage bien développé 55°.	267.10	268.50	D031725	1.40	<0.005		0.001
			268.50	270.00	D031726	1.50	<0.005		0.001
			270.00	271.50	D031727	1.50	<0.005		0.001
			271.50	273.00	D031728	1.50	<0.005		0.001
			273.00	274.50	D031729	1.50	<0.005		0.001
			274.50	276.00	D031731	1.50	0.022		0.022
			276.00	277.50	D031732	1.50	<0.005		0.001
			277.50	279.00	D031734	1.50	<0.005		0.001
			279.00	280.50	D031735	1.50	<0.005		0.001
			280.50	282.00	D031736	1.50	<0.005		0.001
			282.00	283.50	D031737	1.50	0.012		0.012
			283.50	285.00	D031738	1.50	0.013		0.013
			285.00	286.50	D031739	1.50	0.006		0.006
			286.50	288.00	D031740	1.50	0.007		0.007
			288.00	289.50	D031741	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
290.80	308.90	UM <b>Ultramaïfite serpentinisée 70°</b> Ultramaïfite de couleur gris sombre. Altération chloriteuse. Réseau de veine quartz carbonate bien développé. La matrice n'est cependant pas carbonatée en générale. La minéralisation en pyrite est assez bien développé. Le lessivage est moins poussée que l'unité UM supérieure (moins de talc également).	289.50	290.80	D031742	1.30	<0.005		0.001
			290.80	292.50	D031744	1.70	<0.005		0.001
291.30	291.50	FAI <b>Faille 70°</b> Faille associée à une altération carbonate.	292.50	294.00	D031745	1.50	<0.005		0.001
			294.00	295.50	D031746	1.50	<0.005		0.001
			295.50	297.00	D031747	1.50	<0.005		0.001
			297.00	298.40	D031748	1.40	<0.005		0.001
298.40	299.60	FAI <b>Faille 60°</b> Faille qui délimite la zone carbonatée supérieure de l'ultramaïfite de l'ultramaïfite non carbonatée inférieure.	298.40	300.00	D031749	1.60	<0.005		0.001
298.90	299.30	QZVN <b>Veine de Quartz massive 60°</b> Veine de quartz structurellement liée à la faille. Pas de minéralisation associée.	300.00	301.50	D031750	1.50	<0.005		0.001
			301.50	303.00	D031751	1.50	<0.005		0.001
			303.00	304.20	D031752	1.20	<0.005		0.001
			304.20	305.50	D031754	1.30	<0.005		0.001
			305.50	307.20	D031755	1.70	<0.005		0.001
			307.20	308.90	D031756	1.70	<0.005		0.001
308.90	320.00	MS <b>Mudstone</b> Mudstone à litage très bien exprimé 70' en moyenne. Granulo très fine. Couleur fonction du litage (gris pâle, vert, jaunâtre) avec une teinte gris verdâtre dominante.	308.90	310.50	D031757	1.60	0.018		0.018
			310.50	312.00	D031758	1.50	0.057		0.057
			312.00	313.50	D031759	1.50	0.025		0.025
			313.50	315.00	D031760	1.50	0.007		0.007
			315.00	316.50	D031761	1.50	<0.005		0.001
			316.50	318.00	D031762	1.50	0.006		0.006
			318.00	319.00	D031764	1.00	0.009		0.009
			319.00	320.00	D031765	1.00	0.012		0.012
320.00	<b>Fin du sondage</b> Nombre d'échantillons : 191 Nombre d'échantillons QAQC : 27 Longueur totale échantillonnée : 282.80								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
42.00	42.00	D031553	M	0.00	3.370	3.370
55.50	57.00	D031563	D031562	1.50	<0.005	0.001
63.00	63.00	D031570	M1	0.00	<0.005	0.001
67.50	67.50	D031573	J	0.00	0.795	0.795
81.50	83.00	D031583	D031582	1.50	1.195	1.195
94.50	94.50	D031593	K	0.00	1.065	1.065
108.00	109.50	D031603	D031602	1.50	<0.005	0.001
117.10	117.10	D031610	M1	0.00	<0.005	0.001
120.50	120.50	D031613	L	0.00	2.110	2.110
134.00	135.50	D031623	D031622	1.50	<0.005	0.001
147.70	147.70	D031633	M	0.00	2.940	2.940
160.50	162.00	D031643	D031642	1.50	0.010	0.010
169.50	169.50	D031650	M1	0.00	<0.005	0.001
171.90	171.90	D031653	J	0.00	0.856	0.856
185.50	187.00	D031663	D031662	1.50	<0.005	0.001
199.00	199.00	D031673	K	0.00	1.055	1.055
212.50	214.00	D031683	D031682	1.50	0.063	0.063
221.10	221.10	D031690	M1	0.00	<0.005	0.001
224.00	224.00	D031693	L	0.00	2.070	2.070
237.50	239.00	D031703	D031702	1.50	0.250	0.250
251.00	251.00	D031713	M	0.00	3.220	3.220
264.20	265.50	D031723	D031722	1.30	0.015	0.015
273.00	273.00	D031730	M1	0.00	<0.005	0.001
276.00	276.00	D031733	J	0.00	0.799	0.799
289.50	290.80	D031743	D031742	1.30	<0.005	0.001
303.00	303.00	D031753	K	0.00	1.075	1.075
316.50	318.00	D031763	D031762	1.50	0.011	0.011

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-230**

Titre minier :

Section :                      630300

Canton :

Niveau :

Rang :

Place de travail :              Malartic

Foré par :                      Bradley et Frères

Lot :

Décrit par :                      Sylvain SAVADOGO

Du :                              2010-05-26

Date de description :              2010-07-06

Au :                              2010-05-29

Collet

UTM

Azimut :                      180.00°

Plongée :                      -65.00°

Longueur :                      306.00 m

Est                              630 300.3

Nord                              5 374 323.8

Élévation                      297.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	6.00	0.00°	0.00°	Oui
Reflex	9.00	328.70°	-64.10°	Oui
Reflex	12.00	328.10°	-64.40°	Oui
Reflex	15.00	353.90°	-64.50°	Oui
Reflex	18.00	2.90°	-64.60°	Oui
Reflex	21.00	5.50°	-64.50°	Oui
Reflex	24.00	180.90°	-64.60°	Non
Reflex	27.00	179.20°	-64.40°	Non
Reflex	30.00	179.50°	-64.40°	Non
Reflex	33.00	179.20°	-64.50°	Non
Reflex	36.00	180.20°	-64.40°	Non
Reflex	39.00	180.20°	-64.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	42.00	179.70°	-64.80°	Non
Reflex	45.00	179.60°	-64.40°	Non
Reflex	48.00	178.70°	-64.60°	Non
Reflex	51.00	179.70°	-64.40°	Non
Reflex	54.00	180.60°	-64.40°	Non
Reflex	57.00	182.30°	-64.40°	Oui
Reflex	60.00	181.60°	-64.50°	Non
Reflex	63.00	181.20°	-64.50°	Non
Reflex	66.00	181.70°	-64.50°	Non
Reflex	69.00	182.10°	-64.60°	Non
Reflex	72.00	183.30°	-64.80°	Non
Reflex	75.00	183.00°	-64.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	78.00	183.40°	-64.50°	Non	Reflex	177.00	184.70°	-64.20°	Non
Reflex	81.00	183.70°	-64.60°	Non	Reflex	180.00	185.50°	-64.20°	Non
Reflex	84.00	184.70°	-64.60°	Non	Reflex	183.00	185.80°	-64.20°	Non
Reflex	87.00	182.80°	-64.60°	Non	Reflex	186.00	187.60°	-64.20°	Non
Reflex	90.00	182.90°	-64.70°	Non	Reflex	189.00	187.70°	-64.20°	Non
Reflex	93.00	183.40°	-64.60°	Non	Reflex	192.00	185.10°	-64.30°	Non
Reflex	96.00	183.90°	-64.60°	Non	Reflex	195.00	186.00°	-64.20°	Non
Reflex	99.00	183.90°	-65.00°	Non	Reflex	198.00	186.70°	-64.20°	Non
Reflex	102.00	183.50°	-64.70°	Non	Reflex	201.00	186.10°	-64.20°	Non
Reflex	105.00	184.40°	-64.70°	Non	Reflex	204.00	185.80°	-64.20°	Non
Reflex	108.00	184.80°	-64.60°	Non	Reflex	207.00	185.80°	-64.20°	Non
Reflex	111.00	184.30°	-64.60°	Non	Reflex	210.00	185.60°	-64.30°	Non
Reflex	114.00	184.70°	-64.60°	Non	Reflex	213.00	185.60°	-64.20°	Non
Reflex	117.00	185.30°	-64.70°	Non	Reflex	216.00	186.00°	-64.20°	Non
Reflex	120.00	185.60°	-64.70°	Non	Reflex	219.00	187.60°	-64.20°	Oui
Reflex	123.00	185.30°	-64.70°	Non	Reflex	222.00	186.80°	-64.20°	Non
Reflex	126.00	185.40°	-64.60°	Non	Reflex	225.00	187.70°	-64.20°	Non
Reflex	129.00	185.10°	-64.70°	Non	Reflex	228.00	187.40°	-64.20°	Non
Reflex	132.00	185.10°	-64.60°	Non	Reflex	231.00	187.10°	-64.20°	Non
Reflex	135.00	186.00°	-64.70°	Non	Reflex	234.00	188.50°	-64.20°	Non
Reflex	138.00	184.30°	-64.60°	Oui	Reflex	237.00	188.40°	-64.20°	Non
Reflex	141.00	185.10°	-64.50°	Non	Reflex	240.00	187.70°	-64.20°	Non
Reflex	144.00	185.00°	-64.50°	Non	Reflex	243.00	186.80°	-64.20°	Oui
Reflex	147.00	186.50°	-64.40°	Non	Reflex	246.00	189.40°	-64.10°	Non
Reflex	150.00	184.70°	-64.40°	Oui	Reflex	249.00	189.20°	-64.10°	Non
Reflex	153.00	185.30°	-64.40°	Non	Reflex	252.00	189.00°	-64.00°	Non
Reflex	156.00	185.40°	-64.30°	Non	Reflex	255.00	189.90°	-64.00°	Non
Reflex	159.00	184.40°	-64.30°	Non	Reflex	258.00	188.40°	-63.90°	Non
Reflex	162.00	184.70°	-64.30°	Non	Reflex	261.00	189.00°	-63.90°	Non
Reflex	165.00	185.70°	-64.20°	Non	Reflex	264.00	187.90°	-63.90°	Non
Reflex	168.00	184.60°	-64.20°	Oui	Reflex	267.00	188.00°	-63.90°	Non
Reflex	171.00	185.40°	-64.20°	Non	Reflex	270.00	188.90°	-63.80°	Non
Reflex	174.00	184.00°	-64.30°	Non	Reflex	273.00	189.10°	-63.80°	Non



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	6.00	MT <b>Mort-terrain</b> MT							
6.00	17.60	SY <b>Syénite</b> Syénite peu porphyrique avec de phénocristaux de Fp peu hématisé et peu chloriteux, plus ou moins à modérément carbonaté; plus ou moins à modérément hématisé; partiellement peu chloriteux; contenant des zone de passage d'eau; cristaux de pyrite disséminé à 0,2% dans la matrice;							
6.00	222.00	HM05; CB05; CH02 <b>Hématisé 5; Carbonaté 5; Chloriteux 2</b> modérément hématisé; plus ou moins à modérément carbonaté; partiellement peu chloriteux;	6.00	7.50	D035111	1.50	0.026		0.026
			7.50	9.00	D035113	1.50	0.021		0.021
			9.00	10.50	D035114	1.50	<0.005		0.001
			10.50	12.00	D035115	1.50	<0.005		0.001
			12.00	13.50	D035116	1.50	0.006		0.006
			13.50	15.00	D035117	1.50	0.005		0.005
			15.00	16.50	D035118	1.50	0.012		0.012
			16.50	17.60	D035119	1.10	0.011		0.011
18.00	19.00	SY <b>Syénite</b> Syénite peu porphyrique avec de phénocristaux de Fp peu hématisé et peu chloriteux, modérément carbonaté; modérément hématisé; contenant des zone de passage d'eau; cristaux de pyrite disséminé à 0,2% dans la matrice;	18.00	19.00	D035121	1.00	0.007		0.007
19.30	27.00	SY <b>Syénite</b> Syénite peu porphyrique avec de phénocristaux de Fp peu hématisé et peu chloriteux; plus ou moins à modérément carbonaté; plus ou moins à modérément hématisé; partiellement peu chloriteux; contenant des zone de passage d'eau; cristaux de pyrite disséminé à 0,2% dans la matrice;	19.30	21.00	D035122	1.70	0.024		0.024
			21.00	22.50	D035123	1.50	0.014		0.014
			22.50	24.00	D035124	1.50	0.009		0.009
			24.00	25.50	D035125	1.50	0.039		0.039
			25.50	27.00	D035126	1.50	0.057		0.057
27.00	222.00	SY; POR <b>Syénite 40°; Porphyrique</b> syénite porphyrique avec de phenocristaux de Fp majoritaire arondis peu hematisé et peu chloriteux; plus ou moins à modérment carbaonaté, modérément hématisé et peu chloriteux (dans les interstices); cristaux de pyrite disséminé dans la matrice et les veinules de Qz-CC; contenant des vQz-CC, vQz-Tour;	27.00	28.50	D035127	1.50	0.202		0.202
			28.50	30.00	D035128	1.50	<0.005		0.001
			30.00	31.50	D035129	1.50	<0.005		0.001
			31.50	33.00	D035131	1.50	0.005		0.005
			33.00	34.50	D035132	1.50	<0.005		0.001
			34.50	36.00	D035133	1.50	0.017		0.017

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
zone minéralisé à la pyrite disséminée jusqu'à 1% entre 159m et 172,5m;	36.00	37.50	D035134	1.50	<0.005		0.001
	37.50	39.00	D035135	1.50	<0.005		0.001
	39.00	40.50	D035136	1.50	0.021		0.021
	40.50	42.00	D035137	1.50	0.008		0.008
	42.00	43.50	D035138	1.50	0.014		0.014
	43.50	45.00	D035139	1.50	0.006		0.006
	45.00	46.50	D035141	1.50	0.005		0.005
	46.50	48.00	D035142	1.50	0.007		0.007
	48.00	49.50	D035143	1.50	0.009		0.009
	49.50	51.00	D035144	1.50	0.010		0.010
	51.00	52.50	D035145	1.50	<0.005		0.001
	52.50	54.00	D035146	1.50	<0.005		0.001
	54.00	55.50	D035147	1.50	<0.005		0.001
	55.50	57.00	D035148	1.50	0.006		0.006
	57.00	58.50	D035149	1.50	0.007		0.007
	58.50	60.00	D035151	1.50	<0.005		0.001
	60.00	61.50	D035153	1.50	<0.005		0.001
	61.50	63.00	D035154	1.50	<0.005		0.001
	63.00	64.50	D035155	1.50	<0.005		0.001
	64.50	66.00	D035156	1.50	<0.005		0.001
	66.00	67.50	D035157	1.50	0.029		0.029
	67.50	69.00	D035158	1.50	0.006		0.006
	69.00	70.50	D035159	1.50	<0.005		0.001
	70.50	72.00	D035161	1.50	0.005		0.005
	72.00	73.50	D035162	1.50	<0.005		0.001
	73.50	75.00	D035163	1.50	0.005		0.005
	75.00	76.50	D035164	1.50	0.005		0.005
	76.50	78.00	D035165	1.50	0.011		0.011
	78.00	79.50	D035166	1.50	0.010		0.010
	79.50	81.00	D035167	1.50	0.012		0.012
81.00	82.50	D035168	1.50	0.007		0.007	
82.50	84.00	D035169	1.50	0.005		0.005	
84.00	85.50	D035171	1.50	0.009		0.009	

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	85.50	87.00	D035172	1.50	0.006		0.006
	87.00	88.50	D035173	1.50	<0.005		0.001
	88.50	90.00	D035174	1.50	<0.005		0.001
	90.00	91.50	D035175	1.50	<0.005		0.001
	91.50	93.00	D035176	1.50	0.006		0.006
	93.00	94.50	D035177	1.50	<0.005		0.001
	94.50	96.00	D035178	1.50	0.008		0.008
	96.00	97.50	D035179	1.50	0.005		0.005
	97.50	99.00	D035181	1.50	0.014		0.014
	99.00	100.50	D035182	1.50	0.006		0.006
	100.50	102.00	D035183	1.50	0.008		0.008
	102.00	103.50	D035184	1.50	0.495		0.495
	103.50	105.00	D035185	1.50	0.016		0.016
	105.00	106.50	D035186	1.50	0.005		0.005
	106.50	108.00	D035187	1.50	0.006		0.006
	108.00	109.50	D035188	1.50	0.006		0.006
	109.50	111.00	D035189	1.50	0.013		0.013
	111.00	112.50	D035191	1.50	<0.005		0.001
	112.50	114.00	D035193	1.50	0.007		0.007
	114.00	115.50	D035194	1.50	0.008		0.008
	115.50	117.00	D035195	1.50	<0.005		0.001
	117.00	118.50	D035196	1.50	0.006		0.006
	118.50	120.00	D035197	1.50	0.110		0.110
	120.00	121.50	D035198	1.50	0.032		0.032
	121.50	123.00	D035199	1.50	0.012		0.012
	123.00	124.50	D035201	1.50	0.006		0.006
	124.50	126.00	D035202	1.50	<0.005		0.001
	126.00	127.50	D035203	1.50	0.006		0.006
	127.50	129.00	D035204	1.50	<0.005		0.001
	129.00	130.50	D035205	1.50	0.005		0.005
	130.50	132.00	D035206	1.50	0.012		0.012
	132.00	133.50	D035207	1.50	0.006		0.006
	133.50	135.00	D035208	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
142.00	144.00	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminée dans la matrice;	135.00	136.50	D035209	1.50	0.008		0.008
			136.50	138.00	D035211	1.50	0.016		0.016
			138.00	139.50	D035212	1.50	0.010		0.010
			139.50	141.00	D035213	1.50	0.414		0.414
			141.00	142.50	D035214	1.50	0.753		0.753
			142.50	144.00	D035215	1.50	2.180		2.180
			144.00	145.50	D035216	1.50	0.615		0.615
			145.50	147.00	D035217	1.50	0.695		0.695
			147.00	148.50	D035218	1.50	0.111		0.111
			148.50	150.00	D035219	1.50	1.475		1.475
			150.00	151.50	D035221	1.50	0.342		0.342
153.00	154.50	Py00.5 <b>Pyrite 0.5%</b> pyrite disséminé dans la matrice et la veine de Qz;	151.50	153.00	D035222	1.50	0.015		0.015
			153.00	154.50	D035223	1.50	0.669		0.669
			154.50	156.00	D035224	1.50	0.078		0.078
			156.00	157.50	D035225	1.50	0.075		0.075
			157.50	159.00	D035226	1.50	0.040		0.040
159.00	172.50	Py01 <b>Pyrite 1%</b> pyrite disséminée jusqu'à 1% dans la matrice	159.00	160.50	D035227	1.50	0.027		0.027
			160.50	162.00	D035228	1.50	0.954		0.954
			162.00	163.50	D035229	1.50	1.005		1.005
			163.50	165.00	D035231	1.50	1.360		1.360
			165.00	166.50	D035233	1.50	1.130		1.130
			166.50	168.00	D035234	1.50	0.443		0.443
			168.00	169.50	D035235	1.50	1.680		1.680
			169.50	171.00	D035236	1.50	1.305		1.305
			171.00	172.50	D035237	1.50	0.746		0.746
			172.50	174.00	D035238	1.50	0.021		0.021
			174.00	175.50	D035239	1.50	0.079		0.079
			175.50	177.00	D035241	1.50	0.151		0.151
			177.00	178.50	D035242	1.50	0.509		0.509
178.50	180.00	D035243	1.50	0.403		0.403			
180.00	181.50	D035244	1.50	0.025		0.025			
181.50	183.00	D035245	1.50	0.012		0.012			
183.00	184.50	D035246	1.50	1.055		1.055			



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
<b>Pyrite 0.5%</b> pyrite disséminé jusqu'à 0,5% dans la matrice;	184.50	186.00	D035247	1.50	1.105		1.105	
	186.00	187.50	D035248	1.50	1.080		1.080	
	187.50	189.00	D035249	1.50	0.071		0.071	
	189.00	190.50	D035251	1.50	0.108		0.108	
	190.50	192.00	D035252	1.50	0.008		0.008	
	192.00	193.50	D035253	1.50	0.048		0.048	
	193.50	195.00	D035254	1.50	0.006		0.006	
	195.00	196.50	D035255	1.50	0.008		0.008	
	196.50	198.00	D035256	1.50	0.018		0.018	
	198.00	199.50	D035257	1.50	0.019		0.019	
	199.50	201.00	D035258	1.50	0.008		0.008	
	201.00	202.50	D035259	1.50	0.044		0.044	
	202.50	204.00	D035261	1.50	0.070		0.070	
	204.00	205.50	D035262	1.50	0.013		0.013	
	205.50	207.00	D035263	1.50	0.065		0.065	
	207.00	208.50	D035264	1.50	<0.005		0.001	
	208.50	210.00	D035265	1.50	<0.005		0.001	
	210.00	211.50	D035266	1.50	<0.005		0.001	
	211.50	213.00	D035267	1.50	<0.005		0.001	
	213.00	214.50	D035268	1.50	<0.005		0.001	
214.50	216.00	D035269	1.50	<0.005		0.001		
216.00	217.50	D035271	1.50	<0.005		0.001		
217.50	219.00	D035273	1.50	0.087		0.087		
219.00	220.50	D035274	1.50	<0.005		0.001		
220.50	222.00	D035275	1.50	0.090		0.090		
222.00	272.00	SY						
		<b>Syénite</b>						
		syénite , modérément hematisé et peu chloriteux (dans les interstices); cristaux de pyrite disséminé à 0,2% dans la matrice et les veinules de Qz-CC; contenant des vQz-MGT; contact basal 35*AC avec la syénite silicifiée; zone de vQz 30%, miméralisée à la pyrite à 0,8% entre 258m et 259.5						
222.00	273.00	HM05; CH02	222.00	223.50	D035276	1.50	0.124	0.124
		<b>Hématisé 5; Chloriteux 2</b>	223.50	225.00	D035277	1.50	0.035	0.035
		modérément hématisé; peu chloriteux dans les interstices;	225.00	226.50	D035278	1.50	0.182	0.182

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			226.50	228.00	D035279	1.50		0.130		0.130
			228.00	229.50	D035281	1.50		0.012		0.012
			229.50	231.00	D035282	1.50		0.006		0.006
			231.00	232.50	D035283	1.50		0.042		0.042
			232.50	234.00	D035284	1.50		0.046		0.046
			234.00	235.50	D035285	1.50		<0.005		0.001
			235.50	237.00	D035286	1.50		0.054		0.054
			237.00	238.50	D035287	1.50		0.099		0.099
			238.50	240.00	D035288	1.50		0.020		0.020
			240.00	241.50	D035289	1.50		0.007		0.007
			241.50	243.00	D035291	1.50		0.011		0.011
			243.00	244.50	D035292	1.50		<0.005		0.001
			244.50	246.00	D035293	1.50		0.013		0.013
			246.00	247.50	D035294	1.50		<0.005		0.001
			247.50	249.00	D035295	1.50		<0.005		0.001
			249.00	250.50	D035296	1.50		<0.005		0.001
			250.50	252.00	D035297	1.50		<0.005		0.001
			252.00	253.50	D035298	1.50		0.013		0.013
			253.50	255.00	D035299	1.50		<0.005		0.001
			255.00	256.50	D035301	1.50		<0.005		0.001
			256.50	258.00	D035302	1.50		<0.005		0.001
258.00	259.50	Py00.8 <b>Pyrite 0.8%</b> pyrite disséminée jusqu'à 0,8%;	258.00	259.50	D035303	1.50		<0.005		0.001
			259.50	261.00	D035304	1.50		<0.005		0.001
			261.00	262.50	D035305	1.50		0.041		0.041
			262.50	264.00	D035306	1.50		0.084		0.084
			264.00	265.50	D035307	1.50		<0.005		0.001
			265.50	267.00	D035308	1.50		0.046		0.046
			267.00	268.50	D035309	1.50		0.048		0.048
			268.50	270.00	D035311	1.50		0.077		0.077
			270.00	271.50	D035313	1.50		0.094		0.094
			271.50	273.00	D035314	1.50		0.225		0.225
272.00	284.00	SY <b>Syénite 35°</b> syénite silicifiée, plus ou moins hematisé; cristaux de pyrite disséminé								

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		à 0,5% dans la matrice et les veinules de Qz-CC; contenant des vQz, vQz-Tour; Contenant des zones bréchifiées et des zones cataclasées; contact basal graduel et marqué par une zone cataclasée;							
273.00	284.00	SI03; HM03 <b>Silicifié 3; Hématisé 3</b> plus ou moins silicifié; plus ou moins hématisé;							
273.00	306.00	Py03 <b>Pyrite 3%</b> pyrite disséminée entre 0,2 et 0,5% dans la matrice;	273.00	274.50	D035315	1.50	0.559		0.559
			274.50	276.00	D035316	1.50	0.633		0.633
			276.00	277.50	D035317	1.50	0.222		0.222
			277.50	279.00	D035318	1.50	0.189		0.189
			279.00	280.50	D035319	1.50	0.092		0.092
			280.50	282.00	D035321	1.50	0.378		0.378
			282.00	283.00	D035322	1.00	0.532		0.532
			283.00	284.00	D035323	1.00	2.500		2.500
284.00	306.00	MS <b>Mudstone 80°</b> mudstone littée à 80-90°AC, avec des lamination de graphite; peu à plus ou moins chloriteux entre 284m et 294m; modérément carbonaté et partiellement peu chloriteux, entre 294 et 306; cristaux de pyrite disséminée entre 0,2 et 0,5%; contenant des veinules de Qz-CC subperpendiculaires à AC;	284.00	285.00	D035324	1.00	0.524		0.524
			285.00	286.50	D035325	1.50	0.657		0.657
			286.50	288.00	D035326	1.50	0.045		0.045
			288.00	289.50	D035327	1.50	0.243		0.243
			289.50	291.00	D035328	1.50	<0.005		0.001
			291.00	292.50	D035329	1.50	<0.005		0.001
			292.50	294.00	D035331	1.50	0.073		0.073
284.00	294.00	CH03 <b>Chloriteux 3</b> plus ou moins chloriteux;							
294.00	306.00	CB05 <b>Carbonaté 5</b> modérément carbonaté;	294.00	295.50	D035332	1.50	1.330		1.330
			295.50	297.00	D035333	1.50	2.250		2.250
			297.00	298.50	D035334	1.50	0.018		0.018
			298.50	300.00	D035335	1.50	0.009		0.009
			300.00	301.50	D035336	1.50	0.015		0.015
			301.50	303.00	D035337	1.50	0.177		0.177
			303.00	304.50	D035338	1.50	0.051		0.051
			304.50	306.00	D035339	1.50	0.008		0.008

## Corporation Minière Osisko Div. Exploration

306.00

Fin du sondage

Nombre d'échantillons : 201

Nombre d'échantillons QAQC : 29

Longueur totale échantillonnée : 299.30

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	6.00	D035112	M1	0.00	<0.005	0.001
16.50	17.60	D035120	D035119	1.10	0.016	0.016
30.00	30.00	D035130	K	0.00	1.190	1.190
43.50	45.00	D035140	D035139	1.50	0.005	0.005
57.00	57.00	D035150	L	0.00	2.130	2.130
58.50	58.50	D035152	M1	0.00	<0.005	0.001
69.00	70.50	D035160	D035159	1.50	<0.005	0.001
82.50	82.50	D035170	M	0.00	3.300	3.300
96.00	97.50	D035180	D035179	1.50	<0.005	0.001
109.50	109.50	D035190	J	0.00	0.751	0.751
111.00	111.00	D035192	M1	0.00	<0.005	0.001
121.50	123.00	D035200	D035199	1.50	0.008	0.008
135.00	135.00	D035210	K	0.00	1.030	1.030
148.50	150.00	D035220	D035219	1.50	1.465	1.465
162.00	162.00	D035230	L	0.00	2.230	2.230
163.50	163.50	D035232	M1	0.00	<0.005	0.001
174.00	175.50	D035240	D035239	1.50	0.092	0.092
187.50	187.50	D035250	M	0.00	3.040	3.040
201.00	202.50	D035260	D035259	1.50	0.041	0.041
214.50	214.50	D035270	J	0.00	0.740	0.740
216.00	216.00	D035272	M1	0.00	<0.005	0.001
226.50	228.00	D035280	D035279	1.50	0.131	0.131
240.00	240.00	D035290	K	0.00	1.000	1.000
253.50	255.00	D035300	D035299	1.50	<0.005	0.001
267.00	267.00	D035310	L	0.00	1.980	1.980
268.50	268.50	D035312	M1	0.00	<0.005	0.001
279.00	280.50	D035320	D035319	1.50	0.093	0.093
291.00	291.00	D035330	M	0.00	3.220	3.220
304.50	306.00	D035340	D035339	1.50	0.006	0.006

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-231**

Titre minier :

Section :                      630300

Canton :

Niveau :

Foré par :              Bradley et Frères

Rang :

Place de travail :              Malartic

Décrit par :              Sylvain SAVADOGO

Lot :

Du :                      2010-04-29

Date de description :              2010-07-21

Au :                      2010-05-01

Collet

UTM

Azimut :                      180.00°

Plongée :                      -74.00°

Longueur :                      329.00 m

Est                              630 300.2

Nord                              5 374 324.1

Élévation                      297.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	43.10°	-73.70°	Oui
Reflex	8.00	322.20°	-73.90°	Oui
Reflex	11.00	338.80°	-73.90°	Oui
Reflex	14.00	0.10°	-73.70°	Oui
Reflex	17.00	32.20°	-73.90°	Oui
Reflex	20.00	177.70°	-74.00°	Non
Reflex	23.00	175.50°	-73.70°	Non
Reflex	26.00	176.50°	-73.70°	Non
Reflex	29.00	177.70°	-73.70°	Non
Reflex	32.00	176.70°	-73.70°	Non
Reflex	35.00	176.10°	-73.70°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	176.20°	-73.80°	Non
Reflex	41.00	176.10°	-73.70°	Non
Reflex	44.00	175.80°	-73.70°	Non
Reflex	47.00	176.50°	-73.80°	Non
Reflex	50.00	177.10°	-73.70°	Non
Reflex	53.00	176.50°	-73.80°	Non
Reflex	56.00	178.10°	-73.90°	Oui
Reflex	59.00	177.80°	-73.80°	Non
Reflex	62.00	179.70°	-73.80°	Non
Reflex	65.00	179.20°	-73.80°	Non
Reflex	68.00	178.50°	-73.80°	Non
Reflex	71.00	179.90°	-73.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	180.10°	-73.80°	Non	Reflex	173.00	184.10°	-74.00°	Non
Reflex	77.00	179.10°	-73.80°	Non	Reflex	176.00	184.60°	-74.10°	Non
Reflex	80.00	180.50°	-73.90°	Non	Reflex	179.00	184.60°	-74.00°	Non
Reflex	83.00	180.50°	-73.80°	Non	Reflex	182.00	184.10°	-74.00°	Non
Reflex	86.00	180.50°	-73.80°	Non	Reflex	185.00	183.70°	-74.00°	Non
Reflex	89.00	179.50°	-73.80°	Non	Reflex	188.00	184.30°	-74.00°	Non
Reflex	92.00	180.00°	-73.80°	Non	Reflex	191.00	183.90°	-74.00°	Non
Reflex	95.00	181.10°	-73.80°	Non	Reflex	194.00	184.20°	-74.00°	Non
Reflex	98.00	181.10°	-73.90°	Non	Reflex	197.00	184.50°	-74.00°	Non
Reflex	101.00	180.70°	-73.80°	Non	Reflex	200.00	184.30°	-74.00°	Non
Reflex	104.00	180.00°	-73.80°	Non	Reflex	203.00	183.90°	-74.00°	Non
Reflex	107.00	180.30°	-73.80°	Non	Reflex	206.00	184.60°	-74.00°	Non
Reflex	110.00	180.10°	-73.80°	Non	Reflex	209.00	185.30°	-74.10°	Oui
Reflex	113.00	180.10°	-73.80°	Non	Reflex	212.00	184.70°	-74.10°	Non
Reflex	116.00	181.40°	-73.80°	Non	Reflex	215.00	184.50°	-74.10°	Non
Reflex	119.00	181.90°	-73.80°	Non	Reflex	218.00	184.40°	-74.10°	Non
Reflex	122.00	181.60°	-73.80°	Non	Reflex	221.00	184.80°	-74.10°	Non
Reflex	125.00	181.60°	-73.90°	Non	Reflex	224.00	185.30°	-74.00°	Non
Reflex	128.00	182.00°	-73.90°	Non	Reflex	227.00	184.80°	-74.10°	Non
Reflex	131.00	182.00°	-73.90°	Non	Reflex	230.00	185.90°	-74.10°	Non
Reflex	134.00	182.40°	-73.90°	Non	Reflex	233.00	184.80°	-74.00°	Non
Reflex	137.00	182.30°	-73.90°	Non	Reflex	236.00	185.50°	-74.00°	Non
Reflex	140.00	182.20°	-73.90°	Non	Reflex	239.00	184.90°	-74.00°	Non
Reflex	143.00	182.50°	-73.90°	Non	Reflex	242.00	185.80°	-74.00°	Non
Reflex	146.00	182.60°	-73.90°	Non	Reflex	245.00	185.90°	-74.00°	Non
Reflex	149.00	182.40°	-74.00°	Non	Reflex	248.00	185.80°	-74.00°	Non
Reflex	152.00	182.70°	-74.00°	Non	Reflex	251.00	185.50°	-74.00°	Non
Reflex	155.00	182.80°	-74.00°	Non	Reflex	254.00	186.00°	-74.00°	Non
Reflex	158.00	182.80°	-74.00°	Non	Reflex	257.00	184.80°	-74.10°	Non
Reflex	161.00	182.40°	-74.00°	Non	Reflex	260.00	186.90°	-74.10°	Non
Reflex	164.00	180.30°	-74.00°	Oui	Reflex	263.00	186.50°	-74.10°	Non
Reflex	167.00	184.70°	-74.00°	Non	Reflex	266.00	187.20°	-74.00°	Non
Reflex	170.00	184.00°	-74.00°	Non	Reflex	269.00	186.80°	-74.00°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	187.30°	-74.10°	Non					
Reflex	275.00	187.40°	-74.00°	Non					
Reflex	278.00	187.80°	-74.00°	Non					
Reflex	281.00	187.60°	-74.00°	Non					
Reflex	284.00	188.80°	-74.00°	Non					
Reflex	287.00	188.80°	-73.90°	Non					
Reflex	290.00	188.60°	-73.90°	Non					
Reflex	293.00	188.90°	-73.90°	Non					
Reflex	296.00	187.70°	-74.00°	Non					
Reflex	299.00	189.40°	-73.90°	Non					
Reflex	302.00	189.70°	-73.90°	Non					
Reflex	305.00	189.90°	-73.90°	Non					
Reflex	308.00	191.00°	-74.00°	Non					
Reflex	311.00	191.00°	-73.90°	Non					
Reflex	314.00	191.90°	-73.80°	Non					
Reflex	317.00	192.10°	-73.60°	Non					
Reflex	320.00	192.10°	-73.50°	Non					
Reflex	323.00	192.20°	-73.50°	Non					
Reflex	326.00	192.20°	-73.50°	Non					
Reflex	329.00	6.20°	-73.60°	Oui					



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	4.50	MT <b>Mort-terrain</b> MT							
4.50	36.00	SY; POR <b>Syénite; Porphyrique</b> Syénite partiellement peu porphyrique avec de phénocristaux grossiers de FP; modérément carbonaté; modérément hématisée; des passages peu et plus ou moins sericitique et peu à plus ou moins chloriteux; fin cristaux de pyrite disséminée à 0,2%; De 6m à 21m, altération par les eaux météoriques.	4.50	6.00	D045202	1.50	0.008		0.008
			6.00	7.00	D045203	1.00	0.009		0.009
			7.00	8.00	D045204	1.00	0.019		0.019
			8.00	9.50	D045205	1.50	0.008		0.008
			9.50	11.00	D045206	1.50	0.005		0.005
			11.00	12.50	D045207	1.50	<0.005		0.001
			12.50	14.00	D045208	1.50	0.012		0.012
			14.00	15.50	D045209	1.50	0.017		0.017
			15.50	17.00	D045211	1.50	0.081		0.081
			17.00	18.50	D045212	1.50	0.007		0.007
			18.50	20.00	D045213	1.50	0.015		0.015
4.50	20.00	CB05; HM; SR <b>Carbonaté 5; Hématisé; Séricitique</b> modérément carbonaté, hématisé, et partiellement sericitique;							
20.00	26.00	HM05; SR03 <b>Hématisé 5; Séricitique 3</b> modérément hématisé; partiellement sericitique;	20.00	21.50	D045214	1.50	0.019		0.019
			21.50	23.00	D045215	1.50	0.048		0.048
			23.00	24.50	D045216	1.50	0.023		0.023
			24.50	26.00	D045217	1.50	0.016		0.016
26.00	42.00	CB05; SR03; CH03 <b>Carbonaté 5; Séricitique 3; Chloriteux 3</b> modérément carbonaté; partiellement plus ou moins sericitique et partiellement plus ou moins chloriteux;	26.00	27.50	D045218	1.50	0.009		0.009
			27.50	29.00	D045219	1.50	0.011		0.011
			29.00	30.50	D045221	1.50	0.007		0.007
			30.50	32.00	D045222	1.50	0.070		0.070
			32.00	33.50	D045223	1.50	0.006		0.006
			33.50	35.00	D045224	1.50	<0.005		0.001
			35.00	36.00	D045225	1.00	0.034		0.034
36.00	37.10	NR <b>Carotte perdue</b> CNR							
37.10	42.00	SY <b>Syénite</b> Syénite modérément carbonaté; modérément hématisée; des veinules sericitique et chloriteux; fin cristaux de pyrite disséminée à 0,2%;	37.10	38.00	D045226	0.90	0.019		0.019
			38.00	39.50	D045227	1.50	0.012		0.012
			39.50	41.00	D045228	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
42.00	43.00	NR <b>Carotte perdue</b> CNR	41.00	42.00	D045229	1.00	0.035		0.035
42.00	45.50	SI03; SR03 <b>Silicifié 3; Séricitique 3</b> plus ou moins silicifié et plus ou moins sericitique;							
43.00	47.00	SY <b>Syénite</b> Syénite silicifié et sericitique de 43m à 45,5m, ; mais dans l'ensemble, modérément carbonaté; modérément hématisée; des veinules sericitique et chloriteuses; fin cristaux de pyrite disséminée à 0,2%; contenant une veines de Qz-CC-CHL hématisée entre 44m et 44,5m	43.00	44.00	D045231	1.00	0.075		0.075
			44.00	45.50	D045233	1.50	0.065		0.065
45.50	105.00	CB05; HM05; SR03; CH03 <b>Carbonaté 5; Hématisé 5; Séricitique 3; Chloriteux 3</b> modérément carbonaté; modérément hématisé; partiellement peu à plus ou moins sericitique et peu à plus ou moins chloriteux;	45.50	47.00	D045234	1.50	0.014		0.014
47.00	47.80	NR <b>Carotte perdue</b> CNR							
47.80	105.00	SY; POR <b>Syénite; Porphyrique</b> Syénite peu porphyrique avec de phénocristaux grossiers de FP; modérément carbonaté jusqu'à 105,5m; modérément hématisée; des passages peu et plus ou moins sericitique et peu à plus ou moins chloriteux; fin cristaux de pyrite disséminée à 0,2%; contenant des passages cataclasés;	47.80	49.00	D045235	1.20	0.011		0.011
			49.00	50.00	D045236	1.00	<0.005		0.001
			50.00	51.50	D045237	1.50	0.018		0.018
			51.50	53.00	D045238	1.50	0.300		0.300
			53.00	54.50	D045239	1.50	0.818		0.818
			54.50	56.00	D045241	1.50	0.007		0.007
			56.00	57.50	D045242	1.50	<0.005		0.001
			57.50	59.00	D045243	1.50	<0.005		0.001
			59.00	60.50	D045244	1.50	0.361		0.361
			60.50	62.00	D045245	1.50	0.072		0.072
			62.00	63.50	D045246	1.50	0.010		0.010
			63.50	65.00	D045247	1.50	0.144		0.144
			65.00	66.50	D045248	1.50	0.252		0.252
			66.50	68.00	D045249	1.50	0.182		0.182
			68.00	69.50	D045251	1.50	0.491		0.491
			69.50	71.00	D045252	1.50	0.045		0.045

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			71.00	72.50	D045253	1.50		0.047
			72.50	74.00	D045254	1.50		<0.005
			74.00	75.50	D045255	1.50		<0.005
			75.50	77.00	D045256	1.50		<0.005
			77.00	78.50	D045257	1.50		0.009
			78.50	80.00	D045258	1.50		<0.005
			80.00	81.50	D045259	1.50		<0.005
			81.50	83.00	D045261	1.50		<0.005
			83.00	84.50	D045262	1.50		<0.005
			84.50	86.00	D045263	1.50		<0.005
			86.00	87.50	D045264	1.50		<0.005
			87.50	89.00	D045265	1.50		<0.005
			89.00	90.50	D045266	1.50		<0.005
			90.50	92.00	D045267	1.50		0.022
			92.00	93.50	D045268	1.50		0.006
			93.50	95.00	D045269	1.50		<0.005
			95.00	96.50	D045271	1.50		0.041
			96.50	98.00	D045273	1.50		0.399
			98.00	99.50	D045274	1.50		0.051
			99.50	101.00	D045275	1.50		0.035
			101.00	102.50	D045276	1.50		0.161
			102.50	104.00	D045277	1.50		0.033
			104.00	105.50	D045278	1.50		0.072
105.00	236.00	SY; POR	105.50	107.00	D045279	1.50		<0.005
		<b>Syénite; Porphyrique</b>	107.00	108.50	D045281	1.50		0.027
		Syénite très porphyrique avec de phénocristaux grossiers de FP; à	108.50	110.00	D045282	1.50		0.024
		partir de 126.5m modérément carbonaté; modérément hématisée; des	110.00	111.50	D045283	1.50		0.022
		passages peu et plus ou moins sericitique et peu à plus ou moins	111.50	113.00	D045284	1.50		0.036
		chloriteux; fin cristaux de pyrite disséminée à 0,2%;	113.00	114.50	D045285	1.50		0.025
			114.50	116.00	D045286	1.50		0.011
			116.00	117.50	D045287	1.50		0.027
			117.50	119.00	D045288	1.50		0.029
			119.00	120.50	D045289	1.50		0.051

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			120.50	122.00	D045291	1.50		0.067		0.067
			122.00	123.50	D045292	1.50		0.081		0.081
			123.50	125.00	D045293	1.50		0.012		0.012
			125.00	126.50	D045294	1.50		0.038		0.038
105.00	126.50	HM05 <b>Hématisé 5</b> modérément hématisé;								
126.50	236.00	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; modérément hématisé;	126.50	128.00	D045295	1.50		0.014		0.014
			128.00	129.50	D045296	1.50		0.018		0.018
			129.50	131.00	D045297	1.50		0.031		0.031
			131.00	132.50	D045298	1.50		0.022		0.022
			132.50	134.00	D045299	1.50		0.025		0.025
			134.00	135.50	D045301	1.50		0.045		0.045
			135.50	137.00	D045302	1.50		0.029		0.029
			137.00	138.50	D045303	1.50		0.005		0.005
			138.50	140.00	D045304	1.50		<0.005		0.001
			140.00	141.50	D045305	1.50		<0.005		0.001
			141.50	143.00	D045306	1.50		0.005		0.005
			143.00	144.50	D045307	1.50		0.024		0.024
			144.50	146.00	D045308	1.50		0.027		0.027
			146.00	147.50	D045309	1.50		0.013		0.013
			147.50	149.00	D045311	1.50		0.011		0.011
			149.00	150.50	D045313	1.50		0.027		0.027
			150.50	152.00	D045314	1.50		0.021		0.021
			152.00	153.50	D045315	1.50		0.041		0.041
			153.50	155.00	D045316	1.50		0.066		0.066
			155.00	156.50	D045317	1.50		<0.005		0.001
			156.50	158.00	D045318	1.50		0.079		0.079
			158.00	159.50	D045319	1.50		0.048		0.048
			159.50	161.00	D045321	1.50		0.009		0.009
			161.00	162.50	D045322	1.50		0.011		0.011
			162.50	164.00	D045323	1.50		0.005		0.005
			164.00	165.50	D045324	1.50		<0.005		0.001
			165.50	167.00	D045325	1.50		<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	167.00	168.50	D045326	1.50	<0.005		0.001
	168.50	170.00	D045327	1.50	0.005		0.005
	170.00	171.50	D045328	1.50	0.034		0.034
	171.50	173.00	D045329	1.50	0.038		0.038
	173.00	174.50	D045331	1.50	0.134		0.134
	174.50	176.00	D045332	1.50	0.047		0.047
	176.00	177.50	D045333	1.50	0.814		0.814
	177.50	179.00	D045334	1.50	0.038		0.038
	179.00	180.50	D045335	1.50	0.048		0.048
	180.50	182.00	D045336	1.50	0.155		0.155
	182.00	183.50	D045337	1.50	0.186		0.186
	183.50	185.00	D045338	1.50	0.093		0.093
	185.00	186.50	D045339	1.50	0.023		0.023
	186.50	188.00	D045341	1.50	0.038		0.038
	188.00	189.50	D045342	1.50	0.007		0.007
	189.50	191.00	D045343	1.50	0.064		0.064
	191.00	192.50	D045344	1.50	0.058		0.058
	192.50	194.00	D045345	1.50	0.043		0.043
	194.00	195.50	D045346	1.50	0.015		0.015
	195.50	197.00	D045347	1.50	0.007		0.007
	197.00	198.50	D045348	1.50	0.009		0.009
	198.50	200.00	D045349	1.50	0.006		0.006
	200.00	201.50	D045351	1.50	<0.005		0.001
	201.50	203.00	D045353	1.50	0.017		0.017
	203.00	204.50	D045354	1.50	<0.005		0.001
	204.50	206.00	D045355	1.50	<0.005		0.001
	206.00	207.50	D045356	1.50	<0.005		0.001
	207.50	209.00	D045357	1.50	0.008		0.008
	209.00	210.50	D045358	1.50	<0.005		0.001
	210.50	212.00	D045359	1.50	<0.005		0.001
	212.00	213.50	D045361	1.50	<0.005		0.001
	213.50	215.00	D045362	1.50	<0.005		0.001
	215.00	216.50	D045363	1.50	0.057		0.057

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			216.50	218.00	D045364	1.50	0.007		0.007
			218.00	219.50	D045365	1.50	0.008		0.008
			219.50	221.00	D045366	1.50	0.006		0.006
			221.00	222.50	D045367	1.50	0.021		0.021
			222.50	224.00	D045368	1.50	0.009		0.009
			224.00	225.50	D045369	1.50	<0.005		0.001
			225.50	227.00	D045371	1.50	<0.005		0.001
			227.00	228.50	D045372	1.50	0.013		0.013
			228.50	230.00	D045373	1.50	<0.005		0.001
			230.00	231.50	D045374	1.50	0.083		0.083
			231.50	233.00	D045375	1.50	0.010		0.010
			233.00	234.50	D045376	1.50	0.045		0.045
			234.50	236.00	D045377	1.50	0.040		0.040
236.00	257.00	SY; POR <b>Syénite; Porphyrique</b> Syénite peu porphyrique avec de phénocristaux grossiers de FP; avec des passages plus ou moins silicifié et séricitique; modérément hématisée; ; fin cristaux de pyrite disséminée jusqu'à 0,8% dans les passages silicifiés sericitiques et chloriteux;							
236.00	257.00	SI03; HM05; SR03 <b>Silicifié 3; Hématisé 5; Séricitique 3</b> partiellement plus ou moins silicifié et sericitique; modérément hématisé;							
236.00	312.50	Py00.8 <b>Pyrite 0.8%</b> pyrite disséminée dans la matrice des zones silicifiées, sericitiques et chloriteuses, jusqu'à 0,8%;	236.00	237.50	D045378	1.50	0.121		0.121
			237.50	239.00	D045379	1.50	1.050		1.050
			239.00	240.50	D045381	1.50	3.380		3.380
			240.50	242.00	D045382	1.50	1.975		1.975
			242.00	243.50	D045383	1.50	0.334		0.334
			243.50	245.00	D045384	1.50	0.689		0.689
			245.00	246.50	D045385	1.50	0.147		0.147
			246.50	248.00	D045386	1.50	2.770		2.770
			248.00	249.50	D045387	1.50	2.380		2.380
			249.50	251.00	D045388	1.50	1.265		1.265
			251.00	252.50	D045389	1.50	0.805		0.805
			252.50	254.00	D045391	1.50	0.427		0.427

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
257.00	312.50	SY; POR <b>Syénite; Porphyrique</b> Syénite peu porphyrique avec de phénocristaux grossiers de FP; modérément hématisée; partiellement peu et plus ou moins sericitique et peu à plus ou moins chloriteux; carbonaté à partir de 296m; fin cristaux de pyrite disséminée à 0,5% dans certaines zone peu ;a plus ou moins séricitique;	254.00	255.50	D045393	1.50	0.857		0.857
			255.50	257.00	D045394	1.50	0.674		0.674
			257.00	258.50	D045395	1.50	0.222		0.222
			258.50	260.00	D045396	1.50	0.120		0.120
			260.00	261.50	D045397	1.50	0.056		0.056
			261.50	263.00	D045398	1.50	0.167		0.167
			263.00	264.50	D045399	1.50	0.080		0.080
			264.50	266.00	D045401	1.50	0.051		0.051
			266.00	267.50	D045402	1.50	0.052		0.052
			267.50	269.00	D045403	1.50	0.072		0.072
			269.00	270.50	D045404	1.50	0.024		0.024
			270.50	272.00	D045405	1.50	0.222		0.222
			272.00	273.50	D045406	1.50	0.020		0.020
			273.50	275.00	D045407	1.50	0.051		0.051
			275.00	276.50	D045408	1.50	0.005		0.005
			276.50	278.00	D045409	1.50	0.110		0.110
			278.00	279.50	D045411	1.50	0.038		0.038
			279.50	281.00	D045412	1.50	0.007		0.007
			281.00	282.50	D045413	1.50	0.060		0.060
			282.50	284.00	D045414	1.50	0.027		0.027
284.00	285.50	D045415	1.50	0.074		0.074			
285.50	287.00	D045416	1.50	0.024		0.024			
287.00	288.50	D045417	1.50	0.029		0.029			
288.50	290.00	D045418	1.50	0.018		0.018			
290.00	291.50	D045419	1.50	0.084		0.084			
291.50	293.00	D045421	1.50	0.151		0.151			
293.00	294.50	D045422	1.50	0.134		0.134			
294.50	296.00	D045423	1.50	0.045		0.045			
296.00	297.50	D045424	1.50	0.019		0.019			
257.00	297.50	HM05; SR; CH <b>Hématisé 5; Séricitique; Chloriteux</b> modérément hématisé.; peu sericitique et peu chloriteux;							
297.50	312.50	CB05; HM05; SR; CH <b>Carbonaté 5; Hématisé 5; Séricitique; Chloriteux</b>	297.50	299.00	D045425	1.50	0.006		0.006
			299.00	300.50	D045426	1.50	0.229		0.229

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		modérément carbonaté; modérément hématisé; peu sericitique et peu chloriteux;	300.50	302.00	D045427	1.50	0.009		0.009
			302.00	303.50	D045428	1.50	0.029		0.029
			303.50	305.00	D045429	1.50	0.005		0.005
			305.00	306.50	D045431	1.50	0.005		0.005
			306.50	308.00	D045433	1.50	0.006		0.006
			308.00	309.50	D045434	1.50	0.006		0.006
			309.50	311.00	D045435	1.50	0.007		0.007
			311.00	312.50	D045436	1.50	0.027		0.027
312.50	326.00	BA <b>Basalte</b> basalte modérément carbonaté; avec Py disséminée jusqu'à 0,8% dans la matrice; contacts graduels avec la syénite et le siltstone;							
312.50	329.00	CB05 <b>Carbonaté 5</b> modérément carbonaté;							
312.50	329.00	Py00.8 <b>Pyrite 0.8%</b> fin cristaux de Py disséminé jusqu'à 0,8% dans la matrice;	312.50	314.00	D045437	1.50	0.363		0.363
			314.00	315.50	D045438	1.50	0.073		0.073
			315.50	317.00	D045439	1.50	<0.005		0.001
			317.00	318.50	D045441	1.50	<0.005		0.001
			318.50	320.00	D045442	1.50	<0.005		0.001
			320.00	321.50	D045443	1.50	0.005		0.005
			321.50	323.00	D045444	1.50	0.005		0.005
			323.00	324.50	D045445	1.50	<0.005		0.001
			324.50	326.00	D045446	1.50	<0.005		0.001
326.00	329.00	ST <b>Siltstone 50°</b> siltstone modérément carbonaté; peu chloriteux; contenant des laminations de graphite; amas de Py et grain fin de Py jusqu'à 0.8%;	326.00	327.50	D045447	1.50	0.025		0.025
			327.50	329.00	D045448	1.50	0.007		0.007
329.00	Fin du sondage Nombre d'échantillons : 217 Nombre d'échantillons QAQC : 30 Longueur totale échantillonnée : 321.60								



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.00	14.00	D045210	M	0.00	2.730	2.730
27.50	29.00	D045220	D045219	1.50	0.010	0.010
41.00	41.00	D045230	J	0.00	0.722	0.722
43.00	43.00	D045232	M1	0.00	<0.005	0.001
53.00	54.50	D045240	D045239	1.50	0.009	0.009
66.50	66.50	D045250	K	0.00	1.140	1.140
80.00	81.50	D045260	D045259	1.50	0.008	0.008
93.50	93.50	D045270	L	0.00	2.040	2.040
95.00	95.00	D045272	M1	0.00	<0.005	0.001
105.50	107.00	D045280	D045279	1.50	0.020	0.020
119.00	119.00	D045290	M	0.00	3.170	3.170
132.50	134.00	D045300	D045299	1.50	0.054	0.054
146.00	147.50	D045310	J	1.50	0.792	0.792
147.50	149.00	D045312	M1	1.50	<0.005	0.001
158.00	159.50	D045320	D045319	1.50	0.055	0.055
171.50	173.00	D045330	K	1.50	0.795	0.795
185.00	186.50	D045340	D045339	1.50	0.024	0.024
198.50	200.00	D045350	L	1.50	2.040	2.040
200.00	201.50	D045352	M1	1.50	<0.005	0.001
210.50	212.00	D045360	D045359	1.50	<0.005	0.001
224.00	224.00	D045370	M	0.00	3.210	3.210
237.50	239.00	D045380	D045379	1.50	0.987	0.987
251.00	251.00	D045390	J	0.00	0.798	0.798
252.50	252.50	D045392	M1	0.00	0.005	0.005
263.00	264.50	D045400	D045399	1.50	0.075	0.075
276.50	276.50	D045410	K	0.00	1.055	1.055
290.00	291.50	D045420	D045419	1.50	0.085	0.085
303.50	303.50	D045430	L	0.00	2.180	2.180
305.00	305.00	D045432	M1	0.00	0.007	0.007
315.50	317.00	D045440	D045439	1.50	0.005	0.005

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-232**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Ciara Cooke

Lot :

Du :                      2010-05-18

Date de description :

Au :                      2010-05-23

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      488.90 m

Est	631 100.0
Nord	5 374 202.6
Élévation	306.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	359.90°	-59.40°	Non
Reflex	8.00	0.40°	-59.30°	Non
Reflex	11.00	2.00°	-59.70°	Non
Reflex	14.00	1.10°	-59.10°	Non
Reflex	17.00	1.40°	-59.40°	Non
Reflex	20.00	1.50°	-59.20°	Non
Reflex	23.00	1.20°	-59.10°	Non
Reflex	26.00	1.00°	-59.10°	Non
Reflex	29.00	1.20°	-59.00°	Non
Reflex	32.00	1.40°	-58.90°	Non
Reflex	35.00	1.50°	-59.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	1.40°	-58.90°	Non
Reflex	41.00	1.60°	-58.80°	Non
Reflex	44.00	1.80°	-58.90°	Non
Reflex	47.00	2.10°	-59.00°	Non
Reflex	50.00	2.10°	-59.00°	Non
Reflex	53.00	2.10°	-58.90°	Non
Reflex	56.00	2.10°	-58.70°	Non
Reflex	59.00	2.00°	-58.70°	Non
Reflex	62.00	2.20°	-58.70°	Non
Reflex	65.00	2.30°	-58.70°	Non
Reflex	68.00	2.50°	-58.80°	Non
Reflex	71.00	2.60°	-58.80°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	2.70°	-58.80°	Non	Reflex	173.00	3.10°	-55.30°	Non
Reflex	77.00	2.90°	-58.80°	Non	Reflex	176.00	3.10°	-55.20°	Non
Reflex	80.00	3.00°	-58.60°	Non	Reflex	179.00	3.10°	-55.30°	Non
Reflex	83.00	2.80°	-58.10°	Non	Reflex	182.00	3.40°	-55.30°	Non
Reflex	86.00	2.70°	-57.70°	Non	Reflex	185.00	3.50°	-55.30°	Non
Reflex	89.00	2.50°	-57.50°	Non	Reflex	188.00	3.50°	-55.30°	Non
Reflex	92.00	2.60°	-57.40°	Non	Reflex	191.00	3.30°	-55.20°	Non
Reflex	95.00	2.70°	-57.50°	Non	Reflex	194.00	3.90°	-55.20°	Non
Reflex	98.00	2.70°	-57.40°	Non	Reflex	197.00	4.00°	-55.10°	Non
Reflex	101.00	2.70°	-57.50°	Non	Reflex	200.00	4.00°	-55.10°	Non
Reflex	104.00	2.70°	-57.50°	Non	Reflex	203.00	4.30°	-55.20°	Non
Reflex	107.00	2.70°	-57.50°	Non	Reflex	206.00	4.20°	-55.20°	Non
Reflex	110.00	2.80°	-57.50°	Non	Reflex	209.00	4.40°	-55.20°	Non
Reflex	113.00	2.90°	-57.50°	Non	Reflex	212.00	4.60°	-55.30°	Non
Reflex	116.00	2.90°	-57.30°	Non	Reflex	215.00	4.70°	-55.30°	Non
Reflex	119.00	3.00°	-57.40°	Non	Reflex	218.00	4.50°	-55.40°	Non
Reflex	122.00	3.00°	-57.40°	Non	Reflex	221.00	4.80°	-55.30°	Non
Reflex	125.00	3.10°	-57.30°	Non	Reflex	224.00	4.40°	-55.30°	Non
Reflex	128.00	3.20°	-57.20°	Non	Reflex	227.00	5.30°	-55.30°	Non
Reflex	131.00	3.20°	-57.20°	Non	Reflex	230.00	5.30°	-55.30°	Non
Reflex	134.00	3.10°	-57.10°	Non	Reflex	233.00	5.30°	-55.30°	Non
Reflex	137.00	3.10°	-57.00°	Non	Reflex	236.00	5.10°	-55.30°	Non
Reflex	140.00	3.00°	-56.90°	Non	Reflex	239.00	5.60°	-55.30°	Non
Reflex	143.00	2.90°	-56.60°	Non	Reflex	242.00	5.40°	-55.30°	Non
Reflex	146.00	2.60°	-56.20°	Non	Reflex	245.00	5.60°	-55.30°	Non
Reflex	149.00	2.70°	-55.80°	Non	Reflex	248.00	6.10°	-55.40°	Non
Reflex	152.00	2.70°	-55.80°	Non	Reflex	251.00	6.30°	-55.40°	Non
Reflex	155.00	2.70°	-55.60°	Non	Reflex	254.00	6.50°	-55.40°	Non
Reflex	158.00	2.20°	-55.40°	Non	Reflex	257.00	6.70°	-55.40°	Non
Reflex	161.00	3.40°	-55.40°	Non	Reflex	260.00	6.90°	-55.30°	Non
Reflex	164.00	2.60°	-55.30°	Non	Reflex	263.00	6.90°	-55.40°	Non
Reflex	167.00	2.60°	-55.30°	Non	Reflex	266.00	7.20°	-55.40°	Non
Reflex	170.00	2.80°	-55.30°	Non	Reflex	269.00	7.50°	-55.40°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	7.70°	-55.40°	Non
Reflex	275.00	7.70°	-55.40°	Non
Reflex	278.00	7.80°	-55.40°	Non
Reflex	281.00	7.70°	-55.40°	Non
Reflex	284.00	7.90°	-55.40°	Non
Reflex	287.00	7.80°	-55.40°	Non
Reflex	290.00	7.90°	-55.30°	Non
Reflex	293.00	7.90°	-55.30°	Non
Reflex	296.00	7.90°	-55.30°	Non
Reflex	299.00	8.00°	-55.30°	Non
Reflex	302.00	7.90°	-55.20°	Non
Reflex	305.00	8.00°	-55.20°	Non
Reflex	308.00	8.00°	-55.30°	Non
Reflex	311.00	7.90°	-55.20°	Non
Reflex	314.00	8.00°	-55.10°	Non
Reflex	317.00	7.90°	-55.00°	Non
Reflex	320.00	7.90°	-55.00°	Non
Reflex	323.00	7.90°	-55.00°	Non
Reflex	326.00	8.30°	-55.00°	Non
Reflex	329.00	7.70°	-55.00°	Non
Reflex	332.00	7.90°	-55.00°	Non
Reflex	335.00	8.50°	-55.00°	Non
Reflex	338.00	9.20°	-55.00°	Non
Reflex	341.00	6.70°	-55.00°	Oui
Reflex	344.00	10.00°	-55.10°	Non
Reflex	347.00	11.50°	-55.10°	Non
Reflex	350.00	10.00°	-55.00°	Non
Reflex	353.00	10.90°	-55.00°	Non
Reflex	356.00	7.80°	-55.00°	Non
Reflex	359.00	7.10°	-55.00°	Non
Reflex	362.00	10.30°	-54.90°	Non
Reflex	365.00	10.20°	-55.00°	Non
Reflex	368.00	11.80°	-55.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	11.90°	-54.90°	Non
Reflex	374.00	11.80°	-54.90°	Non
Reflex	377.00	11.50°	-54.90°	Non
Reflex	380.00	12.50°	-54.90°	Non
Reflex	383.00	10.80°	-54.90°	Non
Reflex	386.00	11.90°	-54.90°	Non
Reflex	389.00	11.30°	-54.90°	Non
Reflex	392.00	9.50°	-54.80°	Non
Reflex	395.00	8.80°	-54.90°	Non
Reflex	398.00	11.50°	-54.90°	Non
Reflex	401.00	11.50°	-54.80°	Non
Reflex	404.00	11.60°	-54.80°	Non
Reflex	407.00	11.60°	-54.80°	Non
Reflex	410.00	13.00°	-54.80°	Oui
Reflex	413.00	11.00°	-54.80°	Non
Reflex	416.00	11.60°	-54.70°	Non
Reflex	419.00	12.10°	-54.80°	Non
Reflex	422.00	11.50°	-54.70°	Non
Reflex	425.00	11.50°	-54.70°	Non
Reflex	428.00	11.90°	-54.70°	Non
Reflex	431.00	12.00°	-54.70°	Non
Reflex	434.00	11.60°	-54.70°	Non
Reflex	437.00	12.90°	-54.70°	Non
Reflex	440.00	13.60°	-54.70°	Non
Reflex	443.00	13.10°	-54.70°	Non
Reflex	446.00	13.70°	-54.70°	Non
Reflex	449.00	12.10°	-54.70°	Non
Reflex	452.00	13.10°	-54.80°	Non
Reflex	455.00	13.20°	-54.70°	Non
Reflex	458.00	12.10°	-54.80°	Non
Reflex	461.00	12.50°	-54.70°	Non
Reflex	464.00	11.70°	-54.80°	Non
Reflex	467.00	13.10°	-54.80°	Oui

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	12.30°	-54.70°	Non					
Reflex	473.00	12.80°	-54.80°	Non					
Reflex	476.00	11.70°	-54.80°	Non					
Reflex	479.00	13.50°	-54.80°	Non					
Reflex	482.00	13.50°	-54.80°	Non					
Reflex	485.00	8.20°	-54.80°	Oui					
Reflex	488.00	10.20°	-54.80°	Non					
Reflex	490.90	11.90°	-54.80°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
2.00	3.00	MT <b>Mort-terrain</b> Casing, overburden.									
	2.40	8.60	SI04 <b>Silicifié 4</b> Weak pervasive silicification along with elevated conc of sulphides.	2.40	4.00	D040232	1.60	2.970		2.970	
3.00	23.20	SY; POR <b>Syérite; Porphyrique</b> Green-purple grey porphyritic syenite. Localized weak silicification in areas of grey discolouration, associated with elevated conc of sulphides. Localized sericitization and chloritization, areas of pale yellowish-green discolouration. Localized weak hematite alteration, areas of purple discolouration. Localized oxidation. ~3-5% feldspar phenocrysts, pale white-grey to beige colour, mm up to 1cm, sub to anhedral, locally aligned where core is foliated. Irregular, mm stringers of dark green conc chl. Few pale grey to beige qtz-carb stringers, veins. Trace up to 1-2% py.	4.00	5.00	D040234	1.00	1.475			1.475	
			5.00	6.50	D040235	1.50	0.750			0.750	
			6.50	7.50	D040236	1.00	0.023			0.023	
			7.50	8.60	D040237	1.10	0.058			0.058	
	8.60	10.00	SR04 <b>Séricitique 4</b> Pervasive sericite alteration, chl alteration. Patches of weak hem alteration. Localized oxidation.	8.60	9.90	D040238	1.30	0.007			0.007
				9.90	11.00	D040239	1.10	0.022			0.022
	10.00	12.50	HM04 <b>Hématisé 4</b> Weak pervasive hematite alteration.	11.00	12.50	D040240	1.50	0.006			0.006
	12.50	13.10	SR04 <b>Séricitique 4</b> Pervasive sericite alteration, chl alteration. Patches of weak hem alteration.	12.50	14.00	D040241	1.50	<0.005			0.001
	13.10	13.90	HM04 <b>Hématisé 4</b> Weak pervasive hematite alteration.								
	13.90	15.10	SR04 <b>Séricitique 4</b> Pervasive sericite alteration, chl alteration. Patches of weak hem alteration.	14.00	15.10	D040242	1.10	0.006			0.006
	15.10	21.00	HM04 <b>Hématisé 4</b> Pervasive hematite alteration. Localized oxidation.	15.10	16.00	D040244	0.90	<0.005			0.001
				16.00	17.00	D040245	1.00	<0.005			0.001
				17.00	18.50	D040246	1.50	<0.005			0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
18.18	18.32	V ca;30°; <b>Veine de calcite 30°</b> Zone of brecciation, Pale green chloritic matrix with angular purple syenite clasts. 30-45 deg TCA.	18.50	20.00	D040247	1.50	<0.005		0.001
			20.00	21.00	D040248	1.00	<0.005		0.001
21.00	23.20	SR04 <b>Séricitique 4</b> Pervasive sericite alteration, chl alteration. Patches of weak hem alteration. Localized oxidation.	21.00	22.00	D040249	1.00	<0.005		0.001
			22.00	23.20	D040250	1.20	0.091		0.091
23.20	96.00	BA; AMY <b>Basalte 50°; Amygdalaire</b> Pale green-beige basalt. Sericite and chl alteration, bleaching, localized patches of dark green discolouration. Localized weak hematite alteration, pale purple discolouration. Locally silicified with high conc of sulphides. Sharp upper contact at ~50 deg TCA. Pervasively sheared ~20-50 deg TCA. Trace up to 3% qtz filled, mm amygdules. Irregular, dark green, mm chl stringers. Trace up to 0.2-0.5% seam controlled py.	23.20	24.70	D040251	1.50	2.310		2.310
23.20	24.70	SI04 <b>Silicifié 4</b> Pervasive weak silicate alteration, hematite alteration. Localized chl and sericite alteration.	23.20	24.70					
24.70	31.40	SR04 <b>Séricitique 4</b> Patchy moderate sericite and chl alteration, patchy areas of bleaching.	24.70	26.20	D040252	1.50	2.090		2.090
			26.20	27.50	D040254	1.30	0.073		0.073
			27.50	29.00	D040255	1.50	0.011		0.011
			29.00	30.40	D040256	1.40	0.013		0.013
30.40	30.55	V ca;5 cm;50°; <b>Veine de calcite 5 cm 50°</b> Pale greenish-beige qtz carb vein surrounded by bleaching, conc seams of py.	30.40	31.40	D040257	1.00	0.150		0.150
30.83	30.92	V ca;9 cm;55°; <b>Veine de calcite 9 cm 55°</b> Large milky white qtz vein with trace carbs. Conc incl of coarse sulphides.							
31.40	41.50	SR05 <b>Séricitique 5</b> Moderate pervasive bleaching with bands of sericite and chl alteration. Localized strong chl alteration, dark green discolouration. Localized violet discolouration from weak hematite alteration. Localized oxidation.	31.40	32.80	D040258	1.40	0.026		0.026
			32.80	34.00	D040259	1.20	0.392		0.392
			34.00	35.00	D040260	1.00	<0.005		0.001
			35.00	36.00	D040261	1.00	<0.005		0.001
			36.00	37.00	D040262	1.00	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
37.01	37.43	V ca;0 cm;;;50°; <b>Veine de calcite 0 cm 50°</b> Series of large, white-peach qtz-carb veins, oriented 40-50 deg TCA, localized hematite alteration, locally chl rimmed.	37.00	38.00	D040264	1.00	0.023		0.023
37.55	37.72	V ca;7 cm;;;;; <b>Veine de calcite 7 cm 80°</b> White-peach qtz-carb veins, localized hematite alteration, locally chl rimmed.irregular to 80 deg TCA.	38.00	39.50	D040265	1.50	0.193		0.193
38.24	38.44	V ca;;;;; <b>Veine de calcite</b> Zone of brecciation, dark grey silicified matrix with sub-angular to rounded clasts of pale green-beige basalt.	39.50	40.60	D040266	1.10	0.044		0.044
40.22	40.32	V ca;;;55°; <b>Veine de calcite 55°</b> Milky white-blue qtz veins with elevated conc of sulphides, locally brecciated, 55-70 deg TCA.	40.60	41.50	D040267	0.90	0.012		0.012
41.50	44.30	SI05 <b>Silicifié 5</b> Moderate pervasive silicification. Localized sericite, chl and hem alteration.	41.50	43.00	D040268	1.50	0.051		0.051
			43.00	44.30	D040269	1.30	0.053		0.053
44.30	44.70	CH05 <b>Chloriteux 5</b> Moderate pervasive chl alteration, localized sericite and hematite alteration.	44.30	46.00	D040270	1.70	0.026		0.026
44.70	48.50	SI05 <b>Silicifié 5</b> Moderate pervasive silicification, localized patchy sericite, chl and hem alteration.							
46.00	46.11	V ca;11 cm;;;20°; <b>Veine de calcite 11 cm 20°</b> Grey-white to peach qtz-carb vein, incl of conc chl, 20-40 deg TCA.	46.00	47.00	D040271	1.00	0.012		0.012
			47.00	48.50	D040272	1.50	0.395		0.395
48.50	56.00	SR05 <b>Séricitique 5</b> Moderate pervasive bleaching with bands of sericite and chl alteration. Localized strong chl alteration, dark green discolouration. Localized violet discolouration from weak hematite alteration. Localized oxidation.	48.50	50.00	D040274	1.50	0.096		0.096
			50.00	51.50	D040275	1.50	0.009		0.009
			51.50	53.00	D040276	1.50	0.007		0.007
			53.00	54.60	D040277	1.60	0.005		0.005
			54.60	56.00	D040278	1.40	0.013		0.013



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
56.00	57.00	CH06 <b>Chloriteux 6</b> Strong chl alteration with patches of sericite and hem alteration. Localized oxidation.	56.00	57.60	D040279	1.60	0.019		0.019
57.00	60.00	SR05 <b>Séricitique 5</b> Patchy sericite, chl and hem alteration. Localized oxidations. Small patch of weak carbonate alteration.	57.60	59.00	D040280	1.40	0.013		0.013
			59.00	60.00	D040281	1.00	0.014		0.014
60.00	67.80	CH06 <b>Chloriteux 6</b> Moderate to strong pervasive chloritization, localized patches of sericitization and hem alteration. Small localized patches of silicification.	60.00	61.00	D040282	1.00	0.007		0.007
			61.00	62.50	D040284	1.50	0.019		0.019
			62.50	63.40	D040285	0.90	0.028		0.028
			63.40	65.00	D040286	1.60	0.049		0.049
64.00	67.80	V ca;::::; <b>Veine de calcite</b> Zone of brecciation, dark green chloritic matrix supporting pale green, some orangy red, angular clasts of basalt.	65.00	66.50	D040287	1.50	0.024		0.024
			66.50	67.80	D040288	1.30	0.185		0.185
67.80	69.50	SI05 <b>Silicifié 5</b> Moderate pervasive silicification, blue-violet grey discolouration.							
67.80	69.50	V ca;::::; <b>Veine de calcite</b> Zone of brecciation, silicified pale blue-violet grey angular basalt fragments supported by conc seams of py.	67.80	68.60	D040289	0.80	0.584		0.584
			68.60	69.50	D040291	0.90	0.693		0.693
69.50	80.80	SR05 <b>Séricitique 5</b> Moderate pervasive sericite alteration. Localized patches of chl and hem alteration.	69.50	71.00	D040292	1.50	0.104		0.104
			71.00	72.00	D040294	1.00	1.070		1.070
			72.00	73.50	D040295	1.50	2.460		2.460
72.60	72.73	V ca;9 cm;;;40°; <b>Veine de calcite 9 cm 40°</b> White-grey qtz-carb vein, local hem alteration, incl of con chl.	73.50	74.90	D040296	1.40	0.009		0.009
74.20	74.90	V ca;::::; <b>Veine de calcite</b> Zone of brecciation, dark green chloritic matrix with angular frags of purple-grey basalt.	74.90	76.00	D040297	1.10	0.073		0.073
			76.00	77.00	D040298	1.00	<0.005		0.001
			77.00	78.50	D040299	1.50	<0.005		0.001
			78.50	79.40	D040300	0.90	<0.005		0.001
			79.40	80.80	D040301	1.40	0.005		0.005
80.80	96.00	SR05 <b>Séricitique 5</b> Moderate pervasive sericited alteration, chl alteration.	80.80	81.90	D040302	1.10	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description			Analyse								
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)		
81.14	82.12	V ca;::::; <b>Veine de calcite</b> Localized brecciation.	81.90	83.00	D040304	1.10	0.395		0.395		
			83.00	84.40	D040305	1.40	0.005		0.005		
			84.40	86.00	D040306	1.60	<0.005		0.001		
			86.00	86.90	D040307	0.90	0.009		0.009		
			86.90	87.70	D040308	0.80	<0.005		0.001		
			87.70	89.00	D040309	1.30	<0.005		0.001		
			89.00	90.50	D040310	1.50	0.005		0.005		
			90.50	92.00	D040311	1.50	<0.005		0.001		
			92.00	93.50	D040312	1.50	0.086		0.086		
			93.50	95.00	D040314	1.50	0.005		0.005		
			95.00	96.00	D040315	1.00	0.098		0.098		
96.00	104.10	SY; POR <b>Syérite 60°; Porphyrique</b> Pink-red porphyritic syenite intrusion. Sharp contacts, upper ~60 deg TCA, lower ~50 deg TCA. Pervasive, moderate hematite alteration. Localized chl and sericite alteration. 25-30% altered feldspar phenocrysts, pale white-grey to purple-green, eu to subhedral, 2mm up to 2cm, generally oriented along shearing plane ~30-40 deg TCA. Moderate degree of yellowish-white qtz-carb veins, mm up to 3.5cm, irregular and oriented. Localized, mm, eu-subhedral py.									
			96.00	97.00	D040316	1.00	0.081		0.081		
			97.00	97.90	D040317	0.90	0.018		0.018		
			97.90	99.50	D040318	1.60	0.012		0.012		
			99.50	101.00	D040319	1.50	0.014		0.014		
			101.00	102.50	D040320	1.50	0.099		0.099		
			102.50	103.40	D040321	0.90	0.026		0.026		
			103.40	104.20	D040322	0.80	<0.005		0.001		
104.10	158.40	BA; AMY <b>Basalte 50°; Amygdalaire</b> Pale green-beige basalt. Sericite and chl alteration, bleaching, localized patches of dark green discolouration. Localized weak hematite alteration, pale purple discolouration. Locally silicified with high conc of sulphides. Sharp upper contact at ~50 deg TCA. Pervasively sheared ~20-50 deg TCA. Trace up to 3% qtz filled, mm amygdules. Irregular, dark green, mm chl stringers. Trace up to 0.2-0.5% seam controlled py.									

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
104.10	158.40	SR05 <b>Séricitique 5</b> Moderate pervasive bleaching and sericite alteration. Localized chl and hematite alteration (green and purple discoloration, respectively).	104.20	105.70	D040324	1.50	0.008		0.008
			105.70	107.10	D040325	1.40	0.022		0.022
			107.10	108.50	D040326	1.40	0.181		0.181
			108.50	109.50	D040327	1.00	<0.005		0.001
			109.50	111.00	D040328	1.50	<0.005		0.001
			111.00	112.00	D040329	1.00	<0.005		0.001
			112.00	113.00	D040331	1.00	<0.005		0.001
			113.00	114.50	D040332	1.50	0.005		0.005
			114.50	115.50	D040334	1.00	<0.005		0.001
			115.50	116.80	D040335	1.30	0.013		0.013
			116.80	118.00	D040336	1.20	0.860		0.860
			118.00	119.30	D040337	1.30	1.960		1.960
			119.30	121.00	D040338	1.70	0.077		0.077
			121.00	122.00	D040339	1.00	0.005		0.005
			122.00	123.00	D040340	1.00	<0.005		0.001
			123.00	124.00	D040341	1.00	<0.005		0.001
			124.00	125.00	D040342	1.00	<0.005		0.001
			125.00	126.50	D040344	1.50	<0.005		0.001
			126.50	128.00	D040345	1.50	<0.005		0.001
			128.00	129.50	D040346	1.50	<0.005		0.001
129.50	131.00	D040347	1.50	<0.005		0.001			
131.00	132.50	D040348	1.50	<0.005		0.001			
132.05	132.19	V ca; 14 cm;;; 40°; <b>Veine de calcite 14 cm 40°</b> Grey qtz-carb vein, in situ brecciation with pale white qtz carb stringers.	132.50	134.00	D040349	1.50	<0.005		0.001
			134.00	135.50	D040350	1.50	<0.005		0.001
			135.50	137.00	D040351	1.50	<0.005		0.001
			137.00	138.50	D040352	1.50	<0.005		0.001
			138.50	140.00	D040354	1.50	<0.005		0.001
			140.00	141.50	D040355	1.50	<0.005		0.001
			141.50	143.00	D040356	1.50	<0.005		0.001
			143.00	144.50	D040357	1.50	<0.005		0.001
			144.50	146.00	D040358	1.50	<0.005		0.001
			146.00	147.50	D040359	1.50	<0.005		0.001
			147.50	149.00	D040360	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
158.40	163.90	<p>SY</p> <p><b>Syénite 50°</b></p> <p>Purple-red porphyritic syenite. Pervasive moderate to strong hematite alteration, pervasive moderate magnetism. Localized weak to moderate, pervasive carbonate alteration. Localized chl and sericite alteration. Trace-3% altered feldspar phenos, up to 5mm, subhedral, chl and hem altered. Localized brecciation within qtz-carb veins.</p> <p>Traces of py.</p>	149.00	150.00	D040361	1.00	<0.005		0.001
			150.00	151.20	D040362	1.20	<0.005		0.001
			151.20	152.00	D040364	0.80	<0.005		0.001
			152.00	153.50	D040365	1.50	<0.005		0.001
			153.50	155.00	D040366	1.50	<0.005		0.001
			155.00	156.50	D040367	1.50	<0.005		0.001
			156.50	157.80	D040368	1.30	<0.005		0.001
			157.80	158.40	D040369	0.60	<0.005		0.001
			158.40	159.50	D040370	1.10	<0.005		0.001
			159.50	160.30	D040371	0.80	<0.005		0.001
			160.30	162.00	D040372	1.70	0.290		0.290
158.40	162.00	<p>CB03</p> <p><b>Carbonaté 3</b></p> <p>Weak, pervasive carbonate alteration. Moderate pervasive hematite alteration. Localized chl and sericite alteration.</p>							
161.07	161.14	<p>V ca;7 cm;;65°;;</p> <p><b>Veine de calcite 7 cm 65°</b></p> <p>Pale white-grey qtz carb vein, brecciated syenite within, angular clasts, orangy-red to purple-green, up to 2cm. 65-80 deg TCA.</p>							
162.00	163.90	<p>HM04</p> <p><b>Hématisé 4</b></p> <p>Weak to moderate pervasive hematite alteration. Localized chl and sericite alteration.</p>	162.00	162.90	D040374	0.90	0.148		0.148
			162.90	163.90	D040375	1.00	0.125		0.125
163.90	201.00	<p>BA; AMY</p> <p><b>Basalte 60°; Amygdalaire</b></p> <p>Pale green-beige basalt. Sericite and chl alteration, bleaching, localized patches of dark green discolouration. Localized weak hematite alteration, pale purple discolouration. Pervasively sheared ~20-50 deg TCA. Trace up to 3% qtz filled, mm amygdules. Irregular, dark green, mm chl stringers. Seam controlled py.</p>	163.90	165.50	D040376	1.60	0.356		0.356
163.90	187.20	<p>SR05</p> <p><b>Séricitique 5</b></p> <p>Moderate pervasive bleaching, sericite alteration. Localized chl</p>							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
164.11	164.37	and hem alteration (green and purple discolouration, respectively).							
		V ca;::::;	165.50	167.00	D040377	1.50	0.009		0.009
		<b>Veine de calcite</b>	167.00	168.50	D040378	1.50	<0.005		0.001
		Zone of brecciation within bleached and sericitized basalt. Pale green rounded clasts within blue-grey matrix. 50-70 deg TCA.	168.50	170.00	D040379	1.50	<0.005		0.001
			170.00	171.50	D040380	1.50	<0.005		0.001
			171.50	173.00	D040381	1.50	<0.005		0.001
			173.00	174.00	D040382	1.00	<0.005		0.001
			174.00	175.00	D040384	1.00	<0.005		0.001
			175.00	176.70	D040385	1.70	<0.005		0.001
			176.70	178.00	D040386	1.30	<0.005		0.001
			178.00	179.00	D040387	1.00	0.005		0.005
			179.00	180.60	D040388	1.60	0.005		0.005
			180.60	182.00	D040389	1.40	0.158		0.158
			182.00	183.50	D040391	1.50	0.005		0.005
			183.50	185.00	D040392	1.50	<0.005		0.001
			185.00	186.40	D040394	1.40	0.017		0.017
			186.40	187.20	D040395	0.80	<0.005		0.001
187.20	189.40	HM04	187.20	188.20	D040396	1.00	<0.005		0.001
		<b>Hématisé 4</b>	188.20	189.40	D040397	1.20	<0.005		0.001
		Moderate pervasive hem alteration. Patchy sericite and chl alteration.							
189.40	192.90	SR05	189.40	190.20	D040398	0.80	<0.005		0.001
		<b>Séricitique 5</b>	190.20	191.90	D040399	1.70	<0.005		0.001
		Moderate pervasive sericite alteration, localized chl and hem alteration (green and purple discolouration, respectively).	191.90	192.90	D040400	1.00	<0.005		0.001
192.90	195.60	HM05	192.90	194.00	D040401	1.10	<0.005		0.001
		<b>Hématisé 5</b>	194.00	195.60	D040402	1.60	<0.005		0.001
		Moderate pervasive hem alteration. Patchy sericite and chl alteration.							
195.60	201.00	SR05	195.60	196.70	D040404	1.10	0.005		0.005
		<b>Séricitique 5</b>	196.70	197.50	D040405	0.80	<0.005		0.001
		Moderate pervasive sericite alteration. Patchy, locally strong hem and chl alteration.	197.50	199.20	D040406	1.70	<0.005		0.001
198.82	199.20	V ca;::::;	199.20	200.20	D040407	1.00	<0.005		0.001
		<b>Veine de calcite</b>	200.20	201.00	D040408	0.80	3.240		3.240
		Zone of brecciation. Pale beige sericite matrix with angular							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
201.00	490.90	SY; POR <b>Syénite 60°; Porphyrique</b> Deep purple to brick red, porphyritic syenite. Strong, pervasive hematite alteration, pervasive magnetism and dispersed mm grains of spec hem. Localized weak to moderate carbonate alteration. Few localized patches of chl-sericite alteration through network of stringers. Trace up to 5% feldspar phenocrysts, mm up to 2cm, in various stages of chle, sericite, hem alteration, eu-subhedral, generally zoned. Abundant irregular and oriented pale white to grey, locally hem altered, qtz-carb stringers. Irregular, mm seams of conc chl. Localized brecciation. Localized zones of silicate-carbonate flooding accompanied by grey discolouration and conc sulphides. Traces of py.	201.00	201.90	D040409	0.90	0.013		0.013
			201.90	203.40	D040410	1.50	0.159		0.159
			203.40	204.60	D040411	1.20	0.006		0.006
			204.60	206.00	D040412	1.40	<0.005		0.001
201.00	206.00	HM06 <b>Hématisé 6</b> Moderate pervasive hematite alteration (purple to brick red colour). Localized patches of chl and sericite alteration (green discolouration).							
206.00	209.50	CB04 <b>Carbonaté 4</b> Moderate, pervasive carbonate alteration. Pervasive hem alteration.	206.00	207.50	D040414	1.50	<0.005		0.001
206.08	206.16	V ca;4.5 cm;;;;; <b>Veine de calcite 4.5 cm</b> Two pinkish-white qtz-carb veins with inclusions of brecciated red syenite, 2cm and 4.5cm.	207.50	209.00	D040415	1.50	<0.005		0.001
			209.00	210.50	D040416	1.50	<0.005		0.001
209.50	305.00	HM06 <b>Hématisé 6</b> Moderate pervasive hematite alteration (purple to brick red colour). Localized patches of chl and sericite alteration (green discolouration).	210.50	212.00	D040417	1.50	<0.005		0.001
			212.00	213.50	D040418	1.50	<0.005		0.001
			213.50	215.00	D040419	1.50	<0.005		0.001
			215.00	216.50	D040420	1.50	0.013		0.013
			216.50	218.00	D040421	1.50	0.007		0.007
			218.00	219.50	D040422	1.50	0.021		0.021
			219.50	221.00	D040424	1.50	0.013		0.013
			221.00	222.50	D040425	1.50	0.011		0.011
			222.50	224.00	D040426	1.50	0.014		0.014
			224.00	225.50	D040427	1.50	0.027		0.027
225.50	227.00	D040428	1.50	0.704		0.704			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
227.24	227.33	V ca;6 cm;;;;; <b>Veine de calcite 6 cm</b> Pink-white qtz-carb vein with abundance of mm qtz-carb stringers in surrounding area.	227.00	228.50	D040429	1.50	0.051		0.051
			228.50	230.00	D040431	1.50	0.120		0.120
			230.00	231.50	D040432	1.50	0.007		0.007
			231.50	233.00	D040434	1.50	0.010		0.010
			233.00	234.50	D040435	1.50	0.016		0.016
			234.50	236.00	D040436	1.50	<0.005		0.001
			236.00	237.50	D040437	1.50	0.008		0.008
			237.50	239.00	D040438	1.50	0.006		0.006
			239.00	240.50	D040439	1.50	0.330		0.330
			240.50	241.90	D040440	1.40	0.401		0.401
			241.90	243.50	D040441	1.60	0.357		0.357
			243.50	245.00	D040442	1.50	0.707		0.707
			245.00	246.50	D040444	1.50	1.230		1.230
			246.50	248.00	D040445	1.50	0.173		0.173
			248.00	249.50	D040446	1.50	0.056		0.056
			249.50	251.00	D040447	1.50	0.015		0.015
			251.00	252.50	D040448	1.50	0.014		0.014
			252.50	254.00	D040449	1.50	0.015		0.015
			254.00	255.50	D040450	1.50	0.072		0.072
			255.50	257.10	D040451	1.60	0.087		0.087
			257.10	258.40	D040452	1.30	1.180		1.180
			258.40	260.00	D040454	1.60	0.640		0.640
			260.00	261.30	D040455	1.30	1.035		1.035
			261.30	263.00	D040456	1.70	0.054		0.054
			263.00	264.40	D040457	1.40	0.272		0.272
			264.40	266.00	D040458	1.60	0.663		0.663
			266.00	267.50	D040459	1.50	0.189		0.189
			267.50	269.00	D040460	1.50	0.428		0.428
269.00	270.50	D040461	1.50	0.023		0.023			
270.50	272.00	D040462	1.50	0.151		0.151			
272.00	273.20	D040464	1.20	0.022		0.022			
273.20	274.90	D040465	1.70	0.100		0.100			
274.90	276.50	D040466	1.60	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			276.50	278.00	D040467	1.50	<0.005		0.001
			278.00	278.90	D040468	0.90	0.164		0.164
			278.90	279.70	D040469	0.80	0.244		0.244
			279.70	281.00	D040470	1.30	0.045		0.045
			281.00	282.00	D040471	1.00	0.005		0.005
			282.00	283.00	D040472	1.00	<0.005		0.001
			283.00	284.00	D040474	1.00	0.005		0.005
			284.00	285.50	D040475	1.50	0.176		0.176
			285.50	287.00	D040476	1.50	0.356		0.356
			287.00	288.50	D040477	1.50	0.029		0.029
			288.50	290.00	D040478	1.50	0.021		0.021
			290.00	291.50	D040479	1.50	<0.005		0.001
			291.50	293.00	D040480	1.50	0.005		0.005
			293.00	294.50	D040481	1.50	0.121		0.121
			294.50	296.00	D040482	1.50	0.058		0.058
			296.00	297.50	D040484	1.50	0.023		0.023
			297.50	298.80	D040485	1.30	0.015		0.015
			298.80	300.50	D040486	1.70	0.309		0.309
			300.50	302.00	D040487	1.50	0.313		0.313
			302.00	303.50	D040488	1.50	0.278		0.278
			303.50	305.00	D040489	1.50	0.383		0.383
305.00	310.00	CB03	305.00	306.50	D040491	1.50	0.095		0.095
		<b>Carbonaté 3</b>	306.50	308.00	D040492	1.50	0.323		0.323
		Weak pervasive carbonate alteration. Pervasive hem and localized chl alteration.	308.00	309.00	D040494	1.00	0.346		0.346
			309.00	310.00	D040495	1.00	0.144		0.144
310.00	313.70	SY							
		<b>Syénite</b>							
		Pervasively carbonate altered, brecciated syenite. Gradual upper contact, sharp lower contact ~50 deg TCA. Pale to med blue grey with localized zones of chl-sericite alteration (pale yellow-green). Pervasively sheared, ~45-60 deg TCA.							
		Pervasive blue-grey carbonate veins/veinlets/stringers. 0.5 to 1% py, fine disseminated.							
310.00	313.70	CB06							
		<b>Carbonaté 6</b>							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
310.00	313.70	Moderate pervasive carbonate alteration (pervasive blue discolouration). Localized sericite-chl alteration.  V ca;;;45°;; <b>Veine de calcite 45° Pyrite 1%</b>  Zone of pervasively carbonate altered, brecciated syenite. Pervasively sheared, ~45-60 deg TCA. Pervasive blue-grey carbonate veins/veinlets/stringers.	310.00	311.00	D040496	1.00	4.430		4.430
			311.00	312.50	D040497	1.50	4.590		4.590
			312.50	313.70	D040498	1.20	6.830		6.830
313.70	320.00	HM05 <b>Hématité 5</b>  Moderate pervasive hem alteration. Localized chl alteration.	313.70	315.40	D040499	1.70	0.595		0.595
			315.40	317.00	D040500	1.60	0.473		0.473
			317.00	318.50	D040501	1.50	0.340		0.340
			318.50	320.00	D040502	1.50	0.112		0.112
320.00	351.60	CB04 <b>Carbonaté 4</b>  Weak to moderate, pervasive carbonate alteration. Strong pervasive hem alteration (deep purple discolouration).	320.00	321.00	D040504	1.00	1.065		1.065
			321.00	322.00	D040505	1.00	0.279		0.279
			322.00	323.00	D040506	1.00	0.012		0.012
			323.00	324.50	D040507	1.50	<0.005		0.001
			324.50	326.00	D040508	1.50	0.005		0.005
			326.00	328.50	D040509	2.50	0.011		0.011
			328.50	329.00	D040510	0.50	0.008		0.008
326.56	326.61	V ca;4.5 cm;;;60°;; <b>Veine de calcite 4.5 cm 60°</b>  Pale white-grey qtz-carb vein, conc incl of chl.	329.00	330.50	D040511	1.50	<0.005		0.001
			330.50	332.00	D040512	1.50	0.006		0.006
			332.00	333.40	D040514	1.40	0.005		0.005
			333.40	335.00	D040515	1.60	<0.005		0.001
			335.00	336.50	D040516	1.50	0.008		0.008
			336.50	338.00	D040517	1.50	0.008		0.008
			338.00	338.80	D040518	0.80	<0.005		0.001
			338.80	340.00	D040519	1.20	<0.005		0.001
			340.00	341.00	D040520	1.00	<0.005		0.001
			341.00	342.50	D040521	1.50	<0.005		0.001
			342.50	344.00	D040522	1.50	0.018		0.018
			344.00	345.50	D040524	1.50	<0.005		0.001
			345.50	347.00	D040525	1.50	0.005		0.005
			347.00	348.50	D040526	1.50	<0.005		0.001
			348.50	350.00	D040527	1.50	<0.005		0.001
			350.00	351.60	D040528	1.60	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
351.60	356.00	SR03 <b>Séricitique 3</b> Weak sericite, chl and hem alteration.	351.60	353.00	D040529	1.40	0.016		0.016
			353.00	354.70	D040531	1.70	0.049		0.049
			354.70	356.00	D040532	1.30	0.056		0.056
356.00	369.70	CB03 <b>Carbonaté 3</b> Weak pervasive carbonate alteration. Strong pervasive hem alteration.	356.00	357.40	D040534	1.40	2.690		2.690
			357.40	359.00	D040535	1.60	0.193		0.193
			359.00	360.50	D040536	1.50	<0.005		0.001
			360.50	362.00	D040537	1.50	0.013		0.013
			362.00	363.50	D040538	1.50	0.005		0.005
			363.50	365.00	D040539	1.50	0.013		0.013
			365.00	366.50	D040540	1.50	0.006		0.006
365.68	365.71	V ca;3 cm;;;;; <b>Veine de calcite 3 cm 60°</b> 3cm accumulate of 2-3mm white-pink qtz-carb veins, incl of conc chl.	366.50	367.80	D040541	1.30	0.011		0.011
			367.80	368.80	D040542	1.00	0.055		0.055
			368.80	369.70	D040544	0.90	0.049		0.049
369.70	382.60	CB04 <b>Carbonaté 4</b> Weak to moderate pervasive carbonate alteration, strong pervasive hem alteration (dark reddish-purple, pervasive magneitsm), localized chl alteration.	369.70	371.00	D040545	1.30	0.013		0.013
			371.00	372.50	D040546	1.50	0.030		0.030
			372.50	374.10	D040547	1.60	0.934		0.934
374.04	374.12	V ca;;;;; <b>Veine de calcite</b> Irregular grey-pink qtz-carb vein with hem alteration and incl of conc chl.	374.10	375.60	D040548	1.50	0.198		0.198
375.46	375.49	V ca;3.5 cm;;;40°;; <b>Veine de calcite 3.5 cm 40°</b> Pink-grey qtz-carb vein with patches of yellow discolouration, localized hem alteration and incl of conc chl. 30-40 deg TCA.	375.60	376.40	D040549	0.80	0.005		0.005
375.77	375.87	V ca;10 cm;;;50°;; <b>Veine de calcite 10 cm 50°</b> Pink-grey qtz-carb vein with patches of yellow discolouration, localized hem alteration and incl of conc chl.	376.40	377.50	D040550	1.10	0.007		0.007
			377.50	379.00	D040551	1.50	0.012		0.012
			379.00	380.00	D040552	1.00	0.014		0.014
			380.00	381.50	D040554	1.50	<0.005		0.001
			381.50	382.60	D040555	1.10	0.006		0.006
382.60	389.50	SR04 <b>Séricitique 4</b> Weak to moderate pervasive sericite-chl alteration. Weak to moderate hem alteration (magnetic). Very weak carbonate alteration.	382.60	383.50	D040556	0.90	<0.005		0.001
			383.50	385.00	D040557	1.50	0.005		0.005
			385.00	386.00	D040558	1.00	0.006		0.006
			386.00	387.50	D040559	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
389.50	453.50	CB05 <b>Carbonaté 5</b> Weak to moderate pervasive carbonate alteration. Strong pervasive hem alteration (dark red-purple and pervasive magnetism). Localized chl alteration.	387.50	388.50	D040560	1.00	0.005		0.005
			388.50	389.50	D040561	1.00	0.005		0.005
			389.50	390.50	D040562	1.00	0.827		0.827
389.50	389.81	V ca;26 cm;;60°; <b>Veine de calcite 26 cm 60°</b> Large pinkish-white qtz-carb vein. Preceded by 5cm, white-grey-green accumulate of qtz-carb and chl-sericite stringers. Followed by zone of brecciation.							
389.81	393.60	V ca;::::; <b>Veine de calcite</b> Zone of brecciation, white-blue-grey carbonate-silicate flooding resulting in brecciation of red-green syenite.	390.50	392.00	D040564	1.50	1.475		1.475
			392.00	393.60	D040565	1.60	0.766		0.766
			393.60	395.00	D040566	1.40	0.112		0.112
395.00	395.90	V ca;::::; <b>Veine de calcite</b> Brecciated vein. Pale greenish-white-grey brecciated qtz-carb vein, roughly sub-paralle TCA.	395.00	396.50	D040567	1.50	0.216		0.216
			396.50	398.00	D040568	1.50	1.145		1.145
397.00	397.41	V ca;::::; <b>Veine de calcite</b> Zone of brecciation. White-blue-grey qtz-carb flooding.	398.00	399.50	D040569	1.50	0.120		0.120
			399.50	401.00	D040570	1.50	0.076		0.076
			401.00	402.40	D040571	1.40	0.181		0.181
			402.40	404.00	D040572	1.60	0.217		0.217
			404.00	405.40	D040574	1.40	0.048		0.048
			405.40	406.20	D040575	0.80	0.053		0.053
			406.20	407.00	D040576	0.80	0.357		0.357
406.97	407.43	V ca;::::; <b>Veine de calcite</b> Several white-grey qtz-carb veins and patch of carb-silica-chl flooding with minor brecciation.	407.00	408.50	D040577	1.50	0.593		0.593
			408.50	410.00	D040578	1.50	0.663		0.663
			410.00	411.50	D040579	1.50	0.633		0.633
410.83	410.90	V ca;0 cm;::::; <b>Veine de calcite 0 cm</b> White-grey-blue qtz carb vein, minor brecciation and conc seams of sulphides.							
411.17	411.40	V ca;::;40°;; <b>Veine de calcite 40°</b> Zone of carbonate flooding, white-grey-pink carbonates with	411.50	413.00	D040580	1.50	0.227		0.227
			413.00	414.50	D040581	1.50	0.197		0.197

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
		minor brecciation.	414.50	416.00	D040582	1.50	<0.005		0.001
			416.00	417.60	D040584	1.60	0.279		0.279
416.30	416.60	V ca;0 cm;;;30°; <b>Veine de calcite 0 cm 30°</b>	417.60	419.00	D040585	1.40	0.288		0.288
		Zone of silica-carbonate flooding. White-grey qtz-carb veining with brecciated interior.	419.00	420.50	D040586	1.50	<0.005		0.001
			420.50	421.70	D040587	1.20	0.683		0.683
			421.70	423.40	D040588	1.70	0.657		0.657
			423.40	425.00	D040589	1.60	0.145		0.145
			425.00	426.50	D040591	1.50	0.289		0.289
			426.50	428.00	D040592	1.50	0.278		0.278
			428.00	429.50	D040594	1.50	0.109		0.109
			429.50	431.00	D040595	1.50	0.261		0.261
430.07	430.09	V ca;3 cm;;;40°; <b>Veine de calcite 3 cm 40°</b>	431.00	432.50	D040596	1.50	0.120		0.120
		Pink-grey qtz-carb vein, incl of conc chl, hem alteration.	432.50	434.00	D040597	1.50	0.060		0.060
			434.00	435.50	D040598	1.50	0.775		0.775
434.42	434.47	V ca;4 cm;;;; <b>Veine de calcite 4 cm</b>							
		Grey-white-pink qtz-carb vein, hem altered, chl rimmed.							
434.90	434.97	V ca;7 cm;;;; <b>Veine de calcite 7 cm</b>	435.50	437.00	D040599	1.50	0.421		0.421
		Grey-pink qtz-carb vein, localized brecciation, hem and chl alteration.	437.00	438.50	D040600	1.50	<0.005		0.001
			438.50	440.00	D040601	1.50	<0.005		0.001
			440.00	441.50	D040602	1.50	0.005		0.005
			441.50	443.00	D040604	1.50	<0.005		0.001
			443.00	443.80	D040605	0.80	0.009		0.009
443.29	443.61	V ca;34 cm;;;30°; <b>Veine de calcite 34 cm 30°</b>	443.80	445.00	D040606	1.20	<0.005		0.001
		Large white-grey qtz-carb vein, internal mm conc chl seams, localized hem alteration, incl of conc chalcopryrite, incl of conc spec hem.	445.00	446.00	D040607	1.00	<0.005		0.001
			446.00	447.50	D040608	1.50	0.007		0.007
			447.50	449.00	D040609	1.50	0.005		0.005
447.55	447.57	V ca;2 cm;;;70°; <b>Veine de calcite 2 cm 70°</b>	449.00	450.50	D040610	1.50	<0.005		0.001
		White grey qtz carb vein with incl of conc chl and chalcopryrite.	450.50	452.00	D040611	1.50	<0.005		0.001
450.51	450.53	V ca;2 cm;;;50°; <b>Veine de calcite 2 cm 50°</b>	452.00	453.50	D040612	1.50	<0.005		0.001
		Dark green vein of conc chl with 2mm vein of white-grey qtz-carbs.							

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
453.50	455.00	SR04 <b>Séricitique 4</b> Moderate pervasive sericite alteration, localized hem and chl alteration.	453.50	455.00	D040614	1.50	<0.005		0.001
455.00	490.90	CB04 <b>Carbonaté 4</b> Weak to moderate, pervasive carbonate alteration. Moderate to strong pervasive hem alteration, localized chl alteration.	455.00	456.50	D040615	1.50	<0.005		0.001
			456.50	458.00	D040616	1.50	<0.005		0.001
			458.00	459.00	D040617	1.00	0.019		0.019
458.47	458.49	V ca;2 cm;;;75°; <b>Veine de calcite 2 cm 75°</b> 4mm white-grey vein of qtz-carbs with seams of dark green conc chl. Pale pink halo of hem altered qtz-carb. Conc of py.	459.00	460.00	D040618	1.00	<0.005		0.001
			460.00	461.00	D040619	1.00	<0.005		0.001
			461.00	462.50	D040620	1.50	<0.005		0.001
			462.50	463.50	D040621	1.00	0.007		0.007
			463.50	464.50	D040622	1.00	<0.005		0.001
			464.50	466.00	D040624	1.50	<0.005		0.001
			466.00	467.50	D040625	1.50	0.005		0.005
			467.50	469.00	D040626	1.50	<0.005		0.001
			469.00	470.00	D040627	1.00	<0.005		0.001
			470.00	471.50	D040628	1.50	0.051		0.051
470.92	471.20	V ca;;;45°; <b>Veine de calcite 45°</b> Zone of pink grey qtz-carb veining, oriented and irregular, mm up to 1.5 cm. Localized chl inclusions, hem altered. Locally weakly brecciated.	471.50	473.00	D040629	1.50	0.009		0.009
			473.00	474.50	D040631	1.50	0.017		0.017
			474.50	476.00	D040632	1.50	0.063		0.063
			476.00	477.50	D040634	1.50	0.091		0.091
			477.50	479.00	D040635	1.50	0.034		0.034
			479.00	480.60	D040636	1.60	0.119		0.119
			480.60	482.00	D040637	1.40	1.355		1.355
480.70	482.54	V ca;;;65°; <b>Veine de calcite 65°</b> Zone of qtz-carb flooding. Abundant pale pink-grey qtz carb veins, locally brecciated, locally sheared and banded with chl rich seams. 45-65 deg TCA.	482.00	483.50	D040638	1.50	0.074		0.074
			483.50	485.00	D040639	1.50	0.077		0.077
484.28	484.31	V ca;3 cm;;;55°; <b>Veine de calcite 3 cm 55°</b> Yellow-grey qtz carb vein, localized hem and chl alteration.	485.00	486.50	D040640	1.50	0.183		0.183
			486.50	488.00	D040641	1.50	0.231		0.231
486.70	486.74	V ca;3.5 cm;;;35°; <b>Veine de calcite 3.5 cm 35°</b> Pinkish-grey qtz-carb vein, hem altered, chl rimmed. 15 to 35	488.00	489.60	D040642	1.60	0.175		0.175
			489.60	490.90	D040643	1.30	0.149		0.149

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
deg TCA.							
490.90      Fin du sondage Nombre d'échantillons : 363 Nombre d'échantillons QAQC : 49 Longueur totale échantillonnée : 488.50							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
2.40	2.40	D040233	K	0.00	1.055	1.055
14.00	15.10	D040243	D040242	1.10	<0.005	0.001
24.70	24.70	D040253	L	0.00	2.180	2.180
36.00	37.00	D040263	D040262	1.00	<0.005	0.001
47.00	47.00	D040273	M	0.00	3.120	3.120
60.00	61.00	D040283	D040282	1.00	0.009	0.009
67.80	67.80	D040290	M1	0.00	0.005	0.005
69.50	69.50	D040293	J	0.00	0.789	0.789
80.80	81.90	D040303	D040302	1.10	0.010	0.010
92.00	92.00	D040313	K	0.00	0.936	0.936
103.40	104.20	D040323	D040322	0.80	<0.005	0.001
111.00	111.00	D040330	M1	0.00	<0.005	0.001
113.00	113.00	D040333	L	0.00	2.070	2.070
124.00	125.00	D040343	D040342	1.00	<0.005	0.001
137.00	137.00	D040353	M	0.00	3.090	3.090
150.00	151.20	D040363	D040362	1.20	<0.005	0.001
160.30	160.30	D040373	J	0.00	0.736	0.736
173.00	174.00	D040383	D040382	1.00	<0.005	0.001
180.60	180.60	D040390	M1	0.00	<0.005	0.001
183.50	183.50	D040393	K	0.00	1.020	1.020
194.00	195.60	D040403	D040402	1.60	<0.005	0.001
204.60	204.60	D040413	L	0.00	2.110	2.110
218.00	219.50	D040423	D040422	1.50	0.015	0.015
227.00	227.00	D040430	M1	0.00	<0.005	0.001
230.00	230.00	D040433	M	0.00	3.100	3.100
243.50	245.00	D040443	D040442	1.50	0.672	0.672
257.10	257.10	D040453	J	0.00	0.768	0.768
270.50	272.00	D040463	D040462	1.50	0.142	0.142
282.00	282.00	D040473	K	0.00	1.010	1.010
294.50	296.00	D040483	D04082	1.50	0.063	0.063
303.50	303.50	D040490	M1	0.00	<0.005	0.001
306.50	306.50	D040493	L	0.00	2.060	2.060
318.50	320.00	D040503	D040502	1.50	0.102	0.102

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
330.50	330.50	D040513	M	0.00	3.260	3.260
342.50	344.00	D040523	D040522	1.50	0.006	0.006
351.60	351.60	D040530	M1	0.00	<0.005	0.001
354.70	354.70	D040533	J	0.00	0.793	0.793
367.80	368.80	D040543	D040542	1.00	0.056	0.056
379.00	379.00	D040553	K	0.00	1.135	1.135
389.50	390.50	D040563	D040562	1.00	0.835	0.835
402.40	402.40	D040573	L	0.00	2.200	2.200
414.50	416.00	D040583	D040582	1.50	0.005	0.005
423.40	423.40	D040590	M1	0.00	<0.005	0.001
426.50	426.50	D040593	M	0.00	3.120	3.120
440.00	441.50	D040603	D040602	1.50	0.005	0.005
452.00	452.00	D040613	J	0.00	0.747	0.747
463.50	464.50	D040623	D040622	1.00	<0.005	0.001
471.50	471.50	D040630	M1	0.00	<0.005	0.001
474.50	474.50	D040633	K	0.00	1.080	1.080



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-233**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                    A. Jean

Lot :

Du :                              2010-05-23

Date de description :        2010-07-16

Au :                              2010-05-29

Collet

UTM

Azimut :                      0.00°  
 Plongée :                    -68.00°  
 Longueur :                  470.00 m

Est	631 100.0
Nord	5 374 202.8
Élévation	306.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	359.10°	-67.90°	Oui
Reflex	8.00	358.60°	-67.50°	Oui
Reflex	11.00	0.20°	-67.40°	Non
Reflex	14.00	0.90°	-68.00°	Non
Reflex	17.00	0.30°	-67.80°	Non
Reflex	20.00	0.30°	-67.90°	Non
Reflex	23.00	0.30°	-67.80°	Non
Reflex	26.00	359.70°	-67.60°	Non
Reflex	29.00	359.60°	-67.40°	Non
Reflex	32.00	359.70°	-67.60°	Non
Reflex	35.00	359.40°	-67.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.00°	-67.60°	Non
Reflex	41.00	359.40°	-67.40°	Non
Reflex	44.00	359.10°	-67.40°	Non
Reflex	47.00	359.60°	-67.40°	Non
Reflex	50.00	359.60°	-67.00°	Non
Reflex	53.00	359.40°	-67.10°	Non
Reflex	56.00	359.60°	-66.50°	Non
Reflex	59.00	359.60°	-67.10°	Non
Reflex	62.00	359.90°	-66.80°	Non
Reflex	65.00	359.70°	-66.90°	Non
Reflex	68.00	359.60°	-66.50°	Non
Reflex	71.00	0.20°	-66.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.60°	-66.40°	Non	Reflex	173.00	2.70°	-63.80°	Non
Reflex	77.00	1.00°	-66.10°	Non	Reflex	176.00	2.40°	-64.00°	Non
Reflex	80.00	1.20°	-66.00°	Non	Reflex	179.00	3.20°	-64.10°	Non
Reflex	83.00	0.80°	-65.60°	Non	Reflex	182.00	3.00°	-63.90°	Non
Reflex	86.00	1.30°	-65.60°	Non	Reflex	185.00	2.90°	-64.10°	Non
Reflex	89.00	1.10°	-65.50°	Non	Reflex	188.00	2.90°	-64.10°	Non
Reflex	92.00	0.90°	-65.80°	Non	Reflex	191.00	3.00°	-63.70°	Non
Reflex	95.00	1.40°	-65.80°	Non	Reflex	194.00	2.80°	-63.60°	Non
Reflex	98.00	1.50°	-65.70°	Non	Reflex	197.00	3.10°	-63.60°	Non
Reflex	101.00	1.40°	-65.60°	Non	Reflex	200.00	2.50°	-63.50°	Non
Reflex	104.00	1.50°	-65.80°	Non	Reflex	203.00	2.90°	-63.40°	Non
Reflex	107.00	1.10°	-65.60°	Non	Reflex	206.00	3.30°	-63.40°	Non
Reflex	110.00	1.30°	-65.10°	Non	Reflex	209.00	3.00°	-63.70°	Non
Reflex	113.00	1.00°	-65.00°	Non	Reflex	212.00	3.20°	-63.60°	Non
Reflex	116.00	1.20°	-65.00°	Non	Reflex	215.00	3.20°	-63.70°	Non
Reflex	119.00	1.10°	-64.90°	Non	Reflex	218.00	3.30°	-63.60°	Non
Reflex	122.00	1.70°	-65.10°	Non	Reflex	221.00	3.80°	-63.80°	Non
Reflex	125.00	1.60°	-64.80°	Non	Reflex	224.00	4.30°	-63.80°	Non
Reflex	128.00	1.40°	-64.80°	Non	Reflex	227.00	3.70°	-63.70°	Non
Reflex	131.00	1.70°	-65.10°	Non	Reflex	230.00	4.00°	-63.60°	Non
Reflex	134.00	2.00°	-64.90°	Non	Reflex	233.00	4.10°	-63.60°	Non
Reflex	137.00	2.40°	-65.00°	Non	Reflex	236.00	4.80°	-63.90°	Non
Reflex	140.00	2.40°	-65.10°	Non	Reflex	239.00	4.40°	-63.90°	Non
Reflex	143.00	2.50°	-64.80°	Non	Reflex	242.00	4.50°	-63.70°	Non
Reflex	146.00	1.90°	-64.80°	Non	Reflex	245.00	5.10°	-63.80°	Non
Reflex	149.00	2.00°	-64.60°	Non	Reflex	248.00	3.90°	-63.50°	Non
Reflex	152.00	1.90°	-64.60°	Non	Reflex	251.00	5.10°	-64.10°	Non
Reflex	155.00	2.00°	-64.30°	Non	Reflex	254.00	4.00°	-63.80°	Non
Reflex	158.00	2.10°	-64.20°	Non	Reflex	257.00	4.20°	-63.80°	Non
Reflex	161.00	2.60°	-64.30°	Non	Reflex	260.00	6.30°	-64.00°	Non
Reflex	164.00	2.70°	-64.40°	Non	Reflex	263.00	5.00°	-64.10°	Non
Reflex	167.00	2.30°	-64.40°	Non	Reflex	266.00	4.80°	-64.20°	Non
Reflex	170.00	2.70°	-64.20°	Non	Reflex	269.00	4.50°	-64.00°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.30°	-64.10°	Non	Reflex	371.00	6.80°	-63.20°	Non
Reflex	275.00	4.70°	-64.00°	Non	Reflex	374.00	6.50°	-63.10°	Non
Reflex	278.00	5.30°	-64.10°	Non	Reflex	377.00	6.70°	-62.90°	Non
Reflex	281.00	4.90°	-63.90°	Non	Reflex	380.00	6.80°	-62.70°	Non
Reflex	284.00	4.80°	-63.90°	Non	Reflex	383.00	7.00°	-62.90°	Non
Reflex	287.00	5.60°	-63.90°	Non	Reflex	386.00	8.30°	-62.60°	Non
Reflex	290.00	5.40°	-63.80°	Non	Reflex	389.00	9.10°	-62.80°	Non
Reflex	293.00	5.70°	-63.80°	Non	Reflex	392.00	7.10°	-62.50°	Non
Reflex	296.00	5.60°	-64.00°	Non	Reflex	395.00	6.80°	-62.70°	Non
Reflex	299.00	5.40°	-64.00°	Non	Reflex	398.00	6.70°	-62.80°	Non
Reflex	302.00	5.10°	-63.70°	Non	Reflex	401.00	9.30°	-62.50°	Non
Reflex	305.00	5.10°	-63.80°	Non	Reflex	404.00	8.90°	-62.50°	Non
Reflex	308.00	6.00°	-63.80°	Non	Reflex	407.00	6.60°	-62.70°	Oui
Reflex	311.00	5.50°	-63.80°	Non	Reflex	410.00	8.70°	-62.70°	Non
Reflex	314.00	6.30°	-63.70°	Non	Reflex	413.00	7.20°	-62.80°	Non
Reflex	317.00	5.90°	-63.60°	Non	Reflex	416.00	7.40°	-62.40°	Non
Reflex	320.00	6.00°	-63.80°	Non	Reflex	419.00	7.80°	-62.60°	Non
Reflex	323.00	5.80°	-63.60°	Non	Reflex	422.00	7.60°	-62.60°	Non
Reflex	326.00	5.40°	-63.50°	Non	Reflex	425.00	6.80°	-62.30°	Non
Reflex	329.00	6.00°	-63.70°	Non	Reflex	428.00	6.80°	-62.40°	Non
Reflex	332.00	6.00°	-63.60°	Non	Reflex	431.00	7.30°	-62.40°	Non
Reflex	335.00	5.60°	-63.30°	Non	Reflex	434.00	6.50°	-62.30°	Non
Reflex	338.00	5.80°	-63.40°	Non	Reflex	437.00	8.00°	-62.40°	Non
Reflex	341.00	6.30°	-63.50°	Non	Reflex	440.00	6.30°	-62.30°	Non
Reflex	344.00	5.90°	-63.40°	Non	Reflex	443.00	6.70°	-62.30°	Non
Reflex	347.00	5.90°	-63.30°	Non	Reflex	446.00	9.10°	-62.30°	Non
Reflex	350.00	5.80°	-63.10°	Non	Reflex	449.00	8.40°	-62.50°	Non
Reflex	353.00	6.20°	-63.30°	Non	Reflex	452.00	9.00°	-62.50°	Non
Reflex	356.00	6.50°	-63.30°	Non	Reflex	455.00	9.40°	-62.20°	Non
Reflex	359.00	6.40°	-63.20°	Non	Reflex	458.00	9.20°	-62.40°	Non
Reflex	362.00	6.60°	-63.20°	Non	Reflex	461.00	9.40°	-62.60°	Non
Reflex	365.00	6.70°	-63.20°	Non	Reflex	464.00	9.80°	-62.30°	Non
Reflex	368.00	6.70°	-63.20°	Non	Reflex	467.00	9.60°	-62.60°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	0.60°	-62.60°	Oui					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	2.50	MT						
		<b>Mort-terrain</b>						
2.50	26.10	SY	2.50	4.00	D032546	1.50	2.880	2.880
		<b>Syénite</b>						
		De couleur variant de grisâtre à gris-violetée. Les Po sont peu nombreux, peu altérés, plutôt petits avec une texture sub-trachitique par endroits. Nombreux filonnets de chlorite, de 1 à 4 mm d'ép. à 20°AC. La Py est finement disséminée, varaint de tr à 0.2%.	4.00	5.00	D032547	1.00	1.005	1.005
			5.00	6.50	D032548	1.50	1.200	1.200
			6.50	8.00	D032549	1.50	0.139	0.139
			8.00	9.50	D032550	1.50	0.085	0.085
			9.50	11.00	D032551	1.50	0.011	0.011
			11.00	12.50	D032552	1.50	<0.005	0.001
			12.50	14.00	D032554	1.50	<0.005	0.001
			14.00	15.50	D032555	1.50	<0.005	0.001
			15.50	17.00	D032556	1.50	<0.005	0.001
			17.00	18.50	D032557	1.50	<0.005	0.001
			18.50	20.00	D032558	1.50	<0.005	0.001
			20.00	21.50	D032559	1.50	<0.005	0.001
			21.50	23.00	D032560	1.50	<0.005	0.001
			23.00	24.50	D032562	1.50	<0.005	0.001
			24.50	26.10	D032564	1.60	<0.005	0.001
26.10	30.70	BA; BR						
		<b>Basalte 40°; Bréchifié</b>						
		Basalte fortement altéré, silicifié et séricitisé. Les brèches sont bien préservées, de forme prismatiques, de 1 à 4 cm de diam.. La roche est complètement remplacée par la silice de 27.3 à 30.7m avec jusqu'à 0.5% de Py fine disséminée.						
26.10	30.70	FRC	26.10	27.30	D032565	1.20	0.005	0.005
		<b>Fracturé</b>						
27.30	30.70	RE80	27.30	28.50	D032566	1.20	0.010	0.010
		<b>Remplacé (forte silicification) 80</b>						
			28.50	29.70	D032567	1.20	0.073	0.073
			29.70	30.70	D032568	1.00	<0.005	0.001
30.70	81.00	BA						
		<b>Basalte 30°</b>						
		Basalte fortement séricitisé dont on peut deviner qq bordures de coussins cisailées à 25°AC. La séricitisation est très intense par endroits mais on y observe encore qq amygdules de QTZ de 0.5 mm de diam. en moyenne.						

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
30.70	81.00	SR75						
		<b>Séricitique 75</b>						
30.70	81.00	CIS	30.70	32.00	D032569	1.30	0.014	0.014
		<b>Cisaillement 25°</b>	32.00	33.50	D032570	1.50	4.350	4.350
			33.50	35.00	D032571	1.50	0.006	0.006
			35.00	36.50	D032572	1.50	0.007	0.007
			36.50	38.00	D032574	1.50	0.056	0.056
			38.00	39.50	D032575	1.50	0.223	0.223
			39.50	41.00	D032576	1.50	<0.005	0.001
			41.00	42.50	D032577	1.50	<0.005	0.001
			42.50	44.00	D032578	1.50	0.015	0.015
			44.00	45.50	D032579	1.50	0.010	0.010
			45.50	47.00	D032580	1.50	<0.005	0.001
			47.00	48.50	D032581	1.50	0.005	0.005
			48.50	50.00	D032582	1.50	<0.005	0.001
			50.00	51.50	D032584	1.50	0.008	0.008
			51.50	53.00	D032585	1.50	1.360	1.360
			53.00	54.50	D032586	1.50	0.029	0.029
			54.50	56.00	D032587	1.50	0.061	0.061
			56.00	57.50	D032588	1.50	0.010	0.010
			57.50	59.00	D032589	1.50	0.167	0.167
			59.00	60.50	D032590	1.50	0.008	0.008
			60.50	62.00	D032591	1.50	0.020	0.020
			62.00	63.50	D032592	1.50	0.005	0.005
			63.50	65.00	D032594	1.50	0.006	0.006
			65.00	66.50	D032595	1.50	<0.005	0.001
			66.50	68.00	D032596	1.50	0.005	0.005
			68.00	69.50	D032597	1.50	0.005	0.005
			69.50	71.00	D032598	1.50	<0.005	0.001
			71.00	72.50	D032599	1.50	<0.005	0.001
			72.50	74.00	D032600	1.50	<0.005	0.001
			74.00	75.50	D032602	1.50	<0.005	0.001
			75.50	77.00	D032604	1.50	<0.005	0.001
			77.00	78.50	D032605	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
81.00	88.00	BA; BR <b>Basalte 35°; Bréchifié</b> Modérément silicifié avec brèches basaltiques modérément séricitisées. La métastase est modérément à fortement silicifiée.	78.50	80.00	D032606	1.50	0.012		0.012
			80.00	81.00	D032607	1.00	0.008		0.008
81.00	90.85	SI50 <b>Silicifié 50</b>	81.00	82.00	D032608	1.00	0.008		0.008
			82.00	83.00	D032609	1.00	0.010		0.010
			83.00	84.50	D032610	1.50	0.014		0.014
			84.50	86.00	D032611	1.50	0.515		0.515
			86.00	87.00	D032612	1.00	0.056		0.056
			87.00	88.00	D032614	1.00	0.517		0.517
88.00	90.85	BA <b>Basalte 65°</b> Plutôt gris-verdâtre, avec silicification modérée à forte par endroits. Passages dcm également hématisés.	88.00	89.50	D032615	1.50	0.042		0.042
			89.50	90.85	D032616	1.35	0.037		0.037
90.85	98.10	BA <b>Basalte</b> Id. au précédents mais intense silicification (remplacement).	90.85	92.00	D032617	1.15	0.310		0.310
			92.00	93.50	D032618	1.50	0.090		0.090
			93.50	95.00	D032619	1.50	3.800		3.800
			95.00	96.50	D032620	1.50	2.630		2.630
			96.50	98.10	D032621	1.60	6.630		6.630
			98.10	116.20	BA <b>Basalte 55°</b> Intense séricitisation, massive par endroits. On reconnait qq bordures de coussins et amygdules dans une pâte de séricite massive.	98.10	99.50	D032622	1.40
98.10	116.20	SR90 <b>Séricitique 90</b>	99.50	101.00	D032624	1.50	0.008		0.008
			101.00	102.50	D032625	1.50	<0.005		0.001
			102.50	104.00	D032626	1.50	<0.005		0.001
			104.00	105.50	D032627	1.50	0.010		0.010
			105.50	107.00	D032628	1.50	<0.005		0.001
			107.00	108.50	D032629	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
116.20	120.40	BA; BR <b>Basalte; Bréchifié</b> Id. à celui de 81 à 88.0m.	108.50	110.00	D032630	1.50	<0.005		0.001
			110.00	111.50	D032631	1.50	0.005		0.005
			111.50	113.00	D032632	1.50	0.005		0.005
			113.00	114.50	D032634	1.50	0.005		0.005
			114.50	116.20	D032635	1.70	0.798		0.798
116.20	122.70	SI35 <b>Silicifié 35</b>	116.20	117.50	D032636	1.30	0.033		0.033
			117.50	119.00	D032637	1.50	0.005		0.005
			119.00	120.40	D032638	1.40	<0.005		0.001
120.40	122.70	BA <b>Basalte</b> Id. à celui de 88.0 à 90.85m. Plutôt de couleur violacée.	120.40	121.60	D032639	1.20	<0.005		0.001
			121.60	122.70	D032640	1.10	<0.005		0.001
122.70	126.15	BA <b>Basalte</b> Intense silicification avec des veines de qtz-cb aux contacts diffus, 10-25 cm ép. à 30°AC. Séricitisation modérée.	122.70	123.50	D032642	0.80	0.008		0.008
			123.50	125.00	D032644	1.50	0.006		0.006
			125.00	126.15	D032645	1.15	0.012		0.012
126.15	138.50	SY; POR <b>Syérite 35°; Porphyrique</b> Contact net à 35°AC. De couleur rouge, hématisée. Po de Fp nets, en lattes.	126.15	127.00	D032646	0.85	0.005		0.005
			127.00	128.00	D032647	1.00	0.134		0.134
			128.00	129.50	D032648	1.50	0.011		0.011
			129.50	131.00	D032649	1.50	0.029		0.029
			131.00	132.50	D032650	1.50	0.059		0.059
			132.50	134.00	D032651	1.50	0.012		0.012
			134.00	135.50	D032652	1.50	0.100		0.100
			135.50	137.00	D032654	1.50	0.016		0.016
			137.00	138.50	D032655	1.50	0.005		0.005
			138.50	168.00	BA				



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
<b>Basalte 30°</b> Id. à celui de 98.1 à 116.2m. Forte séricitisation avec passages massifs.								
138.50	168.00	SR85	138.50	140.00	D032656	1.50	0.008	0.008
<b>Séricitique 85</b>								
			140.00	141.50	D032657	1.50	0.006	0.006
			141.50	143.00	D032658	1.50	0.009	0.009
			143.00	144.50	D032659	1.50	0.005	0.005
			144.50	146.00	D032660	1.50	<0.005	0.001
			146.00	147.50	D032661	1.50	<0.005	0.001
			147.50	149.00	D032662	1.50	<0.005	0.001
			149.00	150.50	D032664	1.50	<0.005	0.001
			150.50	152.00	D032665	1.50	<0.005	0.001
			152.00	153.50	D032666	1.50	<0.005	0.001
			153.50	155.00	D032667	1.50	<0.005	0.001
			155.00	156.50	D032668	1.50	0.016	0.016
			156.50	158.00	D032669	1.50	<0.005	0.001
			158.00	159.50	D032670	1.50	<0.005	0.001
			159.50	161.00	D032671	1.50	<0.005	0.001
			161.00	162.50	D032672	1.50	<0.005	0.001
			162.50	164.00	D032674	1.50	<0.005	0.001
			164.00	165.50	D032675	1.50	<0.005	0.001
			165.50	167.00	D032676	1.50	<0.005	0.001
			167.00	168.00	D032677	1.00	0.031	0.031
168.00	169.80	BA; BR						
<b>Basalte; Bréchifié</b>								
Forte silicification avec hématisation/séricitisation modérées par endroits.								
168.00	169.80	SI35	168.00	168.90	D032678	0.90	2.270	2.270
<b>Silicifié 35</b>								
			168.90	169.80	D032679	0.90	0.006	0.006
169.80	190.50	BA						
<b>Basalte 55°</b>								
Basalte intensément altéré, passant du rouge (hématisation) au verdâtre (séricitisation) au gris foncé (silicification). Le basalte est totalement remplacé. On devine encore des amygdules par endroits.								
169.80	190.50	SI75; SR30; HM20	169.80	171.50	D032680	1.70	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
Silicifié 75; Séricitique 30; Hématisé 20			171.50	173.00	D032682	1.50	<0.005		0.001
			173.00	174.50	D032684	1.50	0.034		0.034
			174.50	176.00	D032685	1.50	0.233		0.233
			176.00	177.50	D032686	1.50	0.051		0.051
			177.50	179.00	D032687	1.50	0.019		0.019
			179.00	180.50	D032688	1.50	0.005		0.005
			180.50	182.00	D032689	1.50	0.005		0.005
			182.00	183.50	D032690	1.50	<0.005		0.001
			183.50	185.00	D032691	1.50	<0.005		0.001
			185.00	186.50	D032692	1.50	1.390		1.390
			186.50	188.00	D032694	1.50	0.040		0.040
			188.00	189.50	D032695	1.50	0.015		0.015
			189.50	190.50	D032696	1.00	4.330		4.330
190.50	198.00	SY <b>Syénite 40°</b> Contact net à 40 °AC. On reconnaît assez bien les Po de Fp prismatiques. La syénite montre de nombreux filonnets de CB mm dans tous les sens							
190.50	198.00	HM35 <b>Hématisé 35</b>	190.50	191.30	D032697	0.80	0.250		0.250
			191.30	192.50	D032698	1.20	1.215		1.215
			192.50	194.00	D032699	1.50	0.068		0.068
			194.00	195.50	D032700	1.50	0.031		0.031
			195.50	197.00	D032701	1.50	0.011		0.011
			197.00	198.00	D032702	1.00	0.066		0.066
198.00	210.90	BA <b>Basalte</b> Totalemment remplacée, intensément silicifiée et séricitisée. On devine encore qq fantômes d'amygdules, mais le protolithe est excessivement difficile à identifier. La roche varie énormément en couleur, passant du rougeâtre, au beige, au gris foncée, au violacé. Plusieurs passages dcm sont bréchifiés avec nombreuses veines/veinules de CB. Le contact supérieur est progressif alors que le contact inf. est très net mais de forme irrégulière.							
198.00	210.90	SI80; SR50 <b>Silicifié 80; Séricitique 50</b>	198.00	199.00	D032704	1.00	0.021		0.021
			199.00	200.00	D032705	1.00	<0.005		0.001
			200.00	201.50	D032706	1.50	0.012		0.012

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
210.90	223.00	PT <b>Porphyre trachytique 80°</b> Magnifique syénite à texture trachitique à métastase rouge foncée.	201.50	203.00	D032707	1.50	0.023		0.023
			203.00	204.50	D032708	1.50	0.042		0.042
			204.50	206.00	D032709	1.50	<0.005		0.001
			206.00	207.50	D032710	1.50	<0.005		0.001
			207.50	209.00	D032711	1.50	0.315		0.315
			209.00	209.95	D032712	0.95	<0.005		0.001
			209.95	210.90	D032714	0.95	0.005		0.005
210.90	223.00	HM40 <b>Hématisé 40</b>	210.90	212.00	D032715	1.10	<0.005		0.001
			212.00	213.50	D032716	1.50	0.010		0.010
			213.50	215.00	D032717	1.50	0.006		0.006
			215.00	216.50	D032718	1.50	0.008		0.008
			216.50	218.00	D032719	1.50	0.029		0.029
			218.00	219.50	D032720	1.50	0.013		0.013
			219.50	221.00	D032722	1.50	0.167		0.167
			221.00	222.00	D032724	1.00	0.034		0.034
			222.00	223.00	D032725	1.00	0.478		0.478
223.00	228.75	BA <b>Basalte 75°</b> Id. à celle de 198.0 à 210.9. Complètement remplacée/silicifiée et hématisée. Le protolithe est difficile à identifier. Les 2 contacts sont très nets à 75°AC.	223.00	224.00	D032726	1.00	0.999		0.999
			224.00	225.50	D032727	1.50	3.370		3.370
			225.50	227.00	D032728	1.50	1.645		1.645
			227.00	228.75	D032729	1.75	0.907		0.907
			223.00	228.75	SI80; HM50 <b>Silicifié 80; Hématisé 50</b>	223.00	224.00	D032726	1.00
228.75	238.90	SY <b>Syénite 80°</b> Rouge foncé, à texture "pruneau".	228.75	230.00	D032730	1.25	0.110		0.110
			230.00	231.50	D032731	1.50	0.115		0.115
			231.50	233.00	D032732	1.50	0.435		0.435
			233.00	234.50	D032734	1.50	0.148		0.148
228.75	238.90	HM50 <b>Hématisé 50</b>	228.75	230.00	D032730	1.25	0.110		0.110
			230.00	231.50	D032731	1.50	0.115		0.115
			231.50	233.00	D032732	1.50	0.435		0.435
			233.00	234.50	D032734	1.50	0.148		0.148

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			234.50	236.00	D032735	1.50		0.049	0.049
			236.00	237.50	D032736	1.50		0.077	0.077
			237.50	239.00	D032737	1.50		0.036	0.036
238.90	239.55	SY <b>Syénite 40°</b> Fort cisaillement à 40°AC montrant une syénite sans Po..... peut être un dyke de 2 ième génération							
	238.90	239.55	SR40; CH20 <b>Séricitique 40; Chloriteux 20</b>	239.00	240.50	D032738	1.50	<0.005	0.001
239.55	268.80	SY <b>Syénite 40°</b> Syénite rouge comme celle de 228.75 à 238.9 à texture "pruneau"							
	239.55	283.55	HM50 <b>Hématisé 50</b>	240.50	242.00	D032739	1.50	<0.005	0.001
				242.00	243.50	D032740	1.50	<0.005	0.001
				243.50	245.00	D032741	1.50	0.006	0.006
				245.00	246.50	D032742	1.50	0.010	0.010
				246.50	248.00	D032744	1.50	0.331	0.331
				248.00	249.50	D032745	1.50	0.007	0.007
				249.50	251.00	D032746	1.50	0.110	0.110
				251.00	252.50	D032747	1.50	<0.005	0.001
				252.50	254.00	D032748	1.50	<0.005	0.001
				254.00	255.50	D032749	1.50	<0.005	0.001
				255.50	257.00	D032750	1.50	<0.005	0.001
				257.00	258.50	D032751	1.50	<0.005	0.001
				258.50	260.00	D032752	1.50	<0.005	0.001
				260.00	261.50	D032754	1.50	<0.005	0.001
				261.50	263.00	D032755	1.50	<0.005	0.001
				263.00	264.50	D032756	1.50	0.005	0.005
				264.50	266.00	D032757	1.50	<0.005	0.001
				266.00	267.50	D032758	1.50	1.515	1.515
				267.50	269.00	D032759	1.50	0.282	0.282
268.80	283.55	PT <b>Porphyre trachytique 75°</b> Syénite trachitique id. à celle de 210.9 à 223.0 m							
				269.00	270.50	D032760	1.50	0.575	0.575
				270.50	272.00	D032762	1.50	0.227	0.227
				272.00	273.50	D032764	1.50	0.267	0.267
				273.50	275.00	D032765	1.50	0.098	0.098

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
283.55	291.10	BA <b>Basalte 70°</b> Basalte totalement remplacée . Intense silicification et séricitisation moyenne à forte par endroits. Protolithe difficile à identifier.  Id. à 198.0 à 210.9m.	275.00	276.50	D032766	1.50	0.430		0.430
			276.50	278.00	D032767	1.50	0.490		0.490
			278.00	279.50	D032768	1.50	0.298		0.298
			279.50	281.00	D032769	1.50	0.033		0.033
			281.00	282.50	D032770	1.50	0.042		0.042
			282.50	283.55	D032771	1.05	0.019		0.019
			283.55	291.10	SI75; SR30 <b>Silicifié 75; Séricitique 30</b>	283.55	284.35	D032772	0.80
284.35	285.50	D032774				1.15	0.072		0.072
285.50	287.00	D032775				1.50	0.015		0.015
287.00	288.50	D032776				1.50	0.327		0.327
288.50	290.00	D032777				1.50	0.065		0.065
290.00	291.50	D032778				1.50	0.878		0.878
291.10	301.10	BA <b>Basalte</b> Complètement séricitisée. Protolithe probablement basaltique ??????	291.10	301.10					
			291.10	301.10	SR90 <b>Séricitique 90</b>	291.50	293.00	D032779	1.50
291.10	301.10	SR90 <b>Séricitique 90</b>	293.00	294.50	D032780	1.50	0.006		0.006
			294.50	296.00	D032781	1.50	0.378		0.378
			296.00	297.50	D032782	1.50	0.012		0.012
			297.50	299.00	D032784	1.50	0.010		0.010
			299.00	300.00	D032785	1.00	<0.005		0.001
			300.00	301.10	D032786	1.10	<0.005		0.001
			301.10	304.00	BA <b>Basalte 65°</b> Basalte remplacé, fortement silicifié. Contact net à 65 sup et 35°AC inf.	301.10	302.50	D032787	1.40
302.50	304.00	D032788				1.50	1.355		1.355
304.00	307.50	BA; BR	304.00	305.75	D032789	1.75	7.000		7.000

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
307.50	333.45	<p><b>Basalte; Bréchifié</b> Fortement bréchique, complètement blanchi par la silice et possiblement albitisation.</p> <p>BA</p> <p><b>Basalte</b> Basalte fortement altéré, passant du vert au rouge, au jaune, au violacé soulignant une silicification et séricitisation intenses accompagnées par une hématisation locale. On reconnaît encore qq bordures de coussins là où l'altération n'est pas trop intense. Certains passages dcm sont totalement séricitisés. Contact sup. net à 75, inf. net à 30°AC.</p>	307.75	307.50	D032790	1.75	0.383		0.383
307.50	333.45	<p>SI60; SR25; HM10</p> <p><b>Silicifié 60; Séricitique 25; Hématisé 10</b></p>	307.50	308.30	D032791	0.80	0.007		0.007
			308.30	309.50	D032792	1.20	0.006		0.006
			309.50	311.00	D032794	1.50	0.010		0.010
			311.00	312.50	D032795	1.50	0.705		0.705
			312.50	314.00	D032796	1.50	0.019		0.019
			314.00	315.50	D032797	1.50	0.005		0.005
			315.50	317.00	D032798	1.50	0.005		0.005
			317.00	318.50	D032799	1.50	<0.005		0.001
			318.50	320.00	D032800	1.50	0.007		0.007
			320.00	321.50	D032802	1.50	<0.005		0.001
			321.50	323.00	D032804	1.50	0.015		0.015
			323.00	324.50	D032805	1.50	0.005		0.005
			324.50	326.00	D032806	1.50	<0.005		0.001
			326.00	327.50	D032807	1.50	<0.005		0.001
			327.50	329.00	D032808	1.50	0.005		0.005
			329.00	330.50	D032809	1.50	0.009		0.009
			330.50	332.00	D032810	1.50	0.009		0.009
			332.00	333.45	D032811	1.45	0.323		0.323
333.45	470.00	<p>SY; POR</p> <p><b>Syénite; Porphyrique</b> De couleur rouge à rougeâtre, à texture "pruneau". Massive, envahie par qq filonnets de CB. Elle devient rouge-pruneau à partir de 443m.</p> <p>Fin du trou à 470.0 m</p>	333.45	335.00	D032812	1.55	0.015		0.015
			335.00	336.50	D032814	1.50	0.037		0.037
			336.50	338.00	D032815	1.50	0.008		0.008
			338.00	339.50	D032816	1.50	0.075		0.075
			339.50	341.00	D032817	1.50	0.059		0.059
			341.00	342.50	D032818	1.50	0.137		0.137

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			342.50	344.00	D032819	1.50		0.115	0.115
			344.00	345.50	D032820	1.50		0.086	0.086
			345.50	347.00	D032821	1.50		0.028	0.028
			347.00	348.50	D032822	1.50		0.061	0.061
			348.50	350.00	D032824	1.50		0.031	0.031
			350.00	351.50	D032825	1.50		0.195	0.195
			351.50	353.00	D032826	1.50		0.036	0.036
			353.00	354.50	D032827	1.50		0.117	0.117
			354.50	356.00	D032828	1.50		0.023	0.023
			356.00	357.50	D032829	1.50		0.034	0.034
			357.50	359.00	D032830	1.50		0.256	0.256
			359.00	360.50	D032831	1.50		0.094	0.094
			360.50	362.00	D032832	1.50		0.129	0.129
			362.00	363.50	D032834	1.50		0.177	0.177
			363.50	365.00	D032835	1.50		0.081	0.081
			365.00	366.50	D032836	1.50		0.189	0.189
			366.50	368.00	D032837	1.50		0.434	0.434
			368.00	369.50	D032838	1.50		0.538	0.538
			369.50	371.00	D032839	1.50		0.101	0.101
			371.00	372.50	D032840	1.50		0.076	0.076
			372.50	374.00	D032842	1.50		2.100	2.100
333.45	401.80	HM40							
		<b>Hématisé 40</b>							
372.80	377.00	FRC; FAI	374.00	375.50	D032844	1.50		1.070	1.070
		<b>Fracturé 30°; Faille</b>	375.50	377.00	D032845	1.50		0.087	0.087
		Carotte fracturée avec des lits mm à cm de boue de faille à 30°AC.	377.00	378.50	D032846	1.50		0.029	0.029
			378.50	380.00	D032847	1.50		0.012	0.012
			380.00	381.50	D032848	1.50		<0.005	0.001
			381.50	383.00	D032849	1.50		0.033	0.033
			383.00	384.50	D032850	1.50		0.005	0.005
			384.50	386.00	D032851	1.50		<0.005	0.001
			386.00	387.50	D032852	1.50		<0.005	0.001
			387.50	389.00	D032854	1.50		0.015	0.015
			389.00	390.50	D032855	1.50		<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
			390.50	392.00	D032856	1.50		0.005
			392.00	393.50	D032857	1.50		<0.005
			393.50	395.00	D032858	1.50		<0.005
			395.00	396.50	D032859	1.50		<0.005
			396.50	398.00	D032860	1.50		0.007
			398.00	399.50	D032861	1.50		<0.005
			399.50	401.00	D032862	1.50		<0.005
			401.00	402.50	D032864	1.50		<0.005
			402.50	404.00	D032865	1.50		0.017
			404.00	405.50	D032866	1.50		0.032
			405.50	407.00	D032867	1.50		0.005
			407.00	408.50	D032868	1.50		0.006
			408.50	410.00	D032869	1.50		0.021
			410.00	411.50	D032870	1.50		<0.005
			411.50	413.00	D032872	1.50		<0.005
			413.00	414.50	D032874	1.50		<0.005
			414.50	416.00	D032875	1.50		0.065
			416.00	417.50	D032876	1.50		0.015
			417.50	419.00	D032877	1.50		0.058
			419.00	420.50	D032878	1.50		0.096
			420.50	422.00	D032879	1.50		<0.005
			422.00	423.50	D032880	1.50		<0.005
			423.50	425.00	D032881	1.50		0.021
424.40	424.60	CAT	425.00	426.50	D032882	1.50		0.233
		<b>Cataclasé</b>						
		Forte bréchification. COnacts à 50°AC						
425.10	425.40	CAT	426.50	428.00	D032884	1.50		<0.005
		<b>Cataclasé 55°</b>	428.00	429.50	D032885	1.50		0.011
		Bréchification id. à la précédente	429.50	431.00	D032886	1.50		0.105
			431.00	432.50	D032887	1.50		0.316
			432.50	434.00	D032888	1.50		0.203
			434.00	435.50	D032889	1.50		0.090
			435.50	437.00	D032890	1.50		0.017



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
435.70	436.40	IM <b>Intrusion mafique (dyke) 40°</b> Fortement cisailée à 40°AC, chloritisée et fuschite avec inj. de CB. Re présente probablement une zone de cisaillement envahie par un dyke mafique.	437.00	438.50	D032891	1.50	0.012		0.012
			438.50	440.00	D032892	1.50	0.143		0.143
			440.00	441.50	D032894	1.50	0.006		0.006
			441.50	443.00	D032895	1.50	<0.005		0.001
			443.00	444.50	D032896	1.50	<0.005		0.001
			444.50	446.00	D032897	1.50	<0.005		0.001
			446.00	447.50	D032898	1.50	<0.005		0.001
			447.50	449.00	D032899	1.50	<0.005		0.001
			449.00	450.50	D032900	1.50	<0.005		0.001
			450.50	452.00	D032901	1.50	<0.005		0.001
			452.00	453.50	D032902	1.50	<0.005		0.001
			453.50	455.00	D032904	1.50	<0.005		0.001
			455.00	456.50	D032905	1.50	0.006		0.006
			456.50	458.00	D032906	1.50	<0.005		0.001
			458.00	459.50	D032907	1.50	<0.005		0.001
			459.50	461.00	D032908	1.50	<0.005		0.001
			461.00	462.50	D032909	1.50	<0.005		0.001
			462.50	464.00	D032910	1.50	<0.005		0.001
			464.00	465.50	D032912	1.50	<0.005		0.001
			465.50	467.00	D032914	1.50	0.035		0.035
467.00	468.50	D032915	1.50	0.828		0.828			
467.10	467.90	PT <b>Porphyre trachytique 40°</b> Un dyke de syénite trachitique avec contacts nets à 40°AC.	468.50	470.00	D032916	1.50	0.694	0.694	
470.00	<b>Fin du sondage</b> Nombre d'échantillons : 324 Nombre d'échantillons QAQC : 47 Longueur totale échantillonnée : 467.50								

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
11.00	12.50	D032553	D032552	1.50	0.005	0.005
21.50	21.50	D032561	M1	0.00	<0.005	0.001
23.00	23.00	D032563	K	0.00	1.115	1.115
35.00	36.50	D032573	D032572	1.50	0.006	0.006
48.50	48.50	D032583	L	0.00	2.130	2.130
62.00	63.50	D032593	D032592	1.50	0.007	0.007
72.50	72.50	D032601	M1	0.00	<0.005	0.001
74.00	74.00	D032603	M	0.00	3.030	3.030
86.00	87.00	D032613	D032612	1.00	0.067	0.067
98.10	98.10	D032623	J	0.00	0.795	0.795
111.50	113.00	D032633	D032632	1.50	0.005	0.005
121.60	121.60	D032641	M1	0.00	<0.005	0.001
122.70	122.70	D032643	K	0.00	1.140	1.140
134.00	135.50	D032653	D032652	1.50	0.096	0.096
147.50	147.50	D032663	L	0.00	1.995	1.995
161.00	162.50	D032673	D032672	1.50	<0.005	0.001
169.80	169.80	D032681	M1	0.00	<0.005	0.001
171.50	171.50	D032683	M	0.00	2.880	2.880
185.00	186.50	D032693	D032692	1.50	1.470	1.470
197.00	197.00	D032703	J	0.00	0.789	0.789
209.00	209.95	D032713	D032712	0.95	<0.005	0.001
218.00	218.00	D032721	M1	0.00	<0.005	0.001
219.50	219.50	D032723	K	0.00	0.941	0.941
231.50	233.00	D032733	D032732	1.50	0.459	0.459
245.00	245.00	D032743	L	0.00	1.975	1.975
258.50	260.00	D032753	D032752	1.50	<0.005	0.001
269.00	269.00	D032761	M1	0.00	0.006	0.006
270.50	270.50	D032763	M	0.00	3.160	3.160
283.55	284.35	D032773	D032772	0.80	0.107	0.107
296.00	296.00	D032783	J	0.00	0.764	0.764
308.30	309.50	D032793	D032792	1.20	0.006	0.006
318.50	318.50	D032801	M1	0.00	<0.005	0.001
320.00	320.00	D032803	K	0.00	1.110	1.110

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
333.45	335.00	D032813	D032812	1.55	0.021	0.021
347.00	347.00	D032823	L	0.00	2.090	2.090
360.50	362.00	D032833	D032832	1.50	0.229	0.229
371.00	371.00	D032841	M1	0.00	0.007	0.007
372.50	372.50	D032843	M	0.00	2.940	2.940
386.00	387.50	D032853	D032852	1.50	<0.005	0.001
399.50	399.50	D032863	J	0.00	0.789	0.789
410.00	410.00	D032871	M1	0.00	<0.005	0.001
411.50	411.50	D032873	K	0.00	0.987	0.987
425.00	426.50	D032883	D032882	1.50	0.262	0.262
438.50	438.50	D032893	L	0.00	2.050	2.050
452.00	453.50	D032903	D032902	1.50	<0.005	0.001
462.50	462.50	D032911	M1	0.00	<0.005	0.001
464.00	464.00	D032913	M	0.00	3.190	3.190

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-234**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              A. Jean

Lot :

Du :                      2010-05-29

Date de description :              2010-07-18

Au :                      2010-06-03

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      490.30 m

Est	631 100.3
Nord	5 374 249.7
Élévation	308.9

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	358.90°	-60.40°	Non
Reflex	8.00	0.80°	-60.50°	Non
Reflex	11.00	0.00°	-60.60°	Non
Reflex	14.00	0.70°	-60.50°	Non
Reflex	17.00	359.80°	-60.20°	Non
Reflex	20.00	0.10°	-60.20°	Non
Reflex	23.00	1.30°	-60.30°	Non
Reflex	26.00	359.60°	-59.80°	Non
Reflex	29.00	0.30°	-59.70°	Non
Reflex	32.00	359.10°	-59.60°	Non
Reflex	35.00	0.40°	-59.60°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	0.30°	-59.40°	Non
Reflex	41.00	0.70°	-59.30°	Non
Reflex	44.00	0.70°	-59.20°	Non
Reflex	47.00	359.50°	-59.10°	Non
Reflex	50.00	358.90°	-57.80°	Non
Reflex	53.00	1.10°	-58.20°	Non
Reflex	56.00	359.80°	-58.60°	Non
Reflex	59.00	359.60°	-58.60°	Non
Reflex	62.00	1.30°	-58.50°	Non
Reflex	65.00	1.40°	-58.40°	Non
Reflex	68.00	0.30°	-58.20°	Non
Reflex	71.00	0.30°	-58.20°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	1.60°	-58.10°	Oui	Reflex	173.00	358.50°	-55.40°	Non
Reflex	77.00	360.00°	-58.50°	Non	Reflex	176.00	360.00°	-55.40°	Non
Reflex	80.00	359.60°	-58.10°	Non	Reflex	179.00	358.80°	-55.30°	Non
Reflex	83.00	0.20°	-57.70°	Non	Reflex	182.00	358.20°	-55.30°	Non
Reflex	86.00	0.20°	-57.70°	Non	Reflex	185.00	358.90°	-55.20°	Non
Reflex	89.00	359.50°	-57.70°	Non	Reflex	188.00	358.30°	-55.20°	Non
Reflex	92.00	0.90°	-57.60°	Non	Reflex	191.00	358.50°	-55.20°	Non
Reflex	95.00	1.20°	-57.50°	Non	Reflex	194.00	0.30°	-55.20°	Non
Reflex	98.00	0.30°	-57.40°	Non	Reflex	197.00	0.30°	-55.30°	Non
Reflex	101.00	0.80°	-57.50°	Non	Reflex	200.00	358.90°	-55.10°	Non
Reflex	104.00	359.20°	-57.50°	Non	Reflex	203.00	359.80°	-55.10°	Non
Reflex	107.00	359.50°	-57.40°	Non	Reflex	206.00	359.60°	-55.10°	Non
Reflex	110.00	0.00°	-57.10°	Non	Reflex	209.00	359.70°	-55.00°	Non
Reflex	113.00	359.80°	-56.90°	Non	Reflex	212.00	359.40°	-55.00°	Non
Reflex	116.00	358.10°	-56.90°	Non	Reflex	215.00	359.20°	-55.00°	Non
Reflex	119.00	0.40°	-57.40°	Non	Reflex	218.00	359.80°	-55.10°	Non
Reflex	122.00	358.40°	-56.50°	Non	Reflex	221.00	359.00°	-55.00°	Non
Reflex	125.00	358.40°	-56.30°	Non	Reflex	224.00	359.20°	-55.00°	Non
Reflex	128.00	358.80°	-56.00°	Non	Reflex	227.00	0.60°	-55.00°	Non
Reflex	131.00	355.60°	-56.00°	Oui	Reflex	230.00	0.10°	-55.20°	Non
Reflex	134.00	359.40°	-55.90°	Non	Reflex	233.00	358.70°	-55.10°	Non
Reflex	137.00	359.40°	-55.70°	Non	Reflex	236.00	0.80°	-55.10°	Non
Reflex	140.00	359.30°	-55.70°	Non	Reflex	239.00	0.80°	-55.10°	Non
Reflex	143.00	359.50°	-55.80°	Non	Reflex	242.00	0.20°	-55.10°	Non
Reflex	146.00	358.40°	-55.80°	Non	Reflex	245.00	355.10°	-52.60°	Oui
Reflex	149.00	357.70°	-55.70°	Non	Reflex	248.00	1.40°	-55.10°	Non
Reflex	152.00	357.90°	-55.70°	Non	Reflex	251.00	0.20°	-55.00°	Non
Reflex	155.00	359.30°	-55.50°	Non	Reflex	254.00	359.50°	-55.00°	Non
Reflex	158.00	359.60°	-55.60°	Non	Reflex	257.00	359.20°	-54.90°	Non
Reflex	161.00	357.90°	-55.60°	Non	Reflex	260.00	0.10°	-54.90°	Non
Reflex	164.00	359.70°	-55.50°	Non	Reflex	263.00	0.10°	-55.00°	Non
Reflex	167.00	358.50°	-55.30°	Non	Reflex	266.00	1.80°	-54.90°	Non
Reflex	170.00	358.50°	-55.30°	Non	Reflex	269.00	2.90°	-54.90°	Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	1.40°	-54.80°	Non
Reflex	275.00	1.10°	-54.70°	Non
Reflex	278.00	359.90°	-54.80°	Non
Reflex	281.00	0.60°	-54.70°	Non
Reflex	284.00	2.40°	-54.70°	Non
Reflex	287.00	2.40°	-54.80°	Non
Reflex	290.00	2.30°	-54.70°	Non
Reflex	293.00	0.40°	-54.80°	Non
Reflex	296.00	359.80°	-54.70°	Non
Reflex	299.00	3.40°	-54.70°	Oui
Reflex	302.00	1.70°	-54.70°	Non
Reflex	305.00	358.40°	-54.60°	Non
Reflex	308.00	0.20°	-54.60°	Non
Reflex	311.00	0.80°	-54.60°	Non
Reflex	314.00	0.10°	-54.60°	Non
Reflex	317.00	359.00°	-54.60°	Non
Reflex	320.00	358.70°	-54.70°	Non
Reflex	323.00	360.00°	-54.60°	Non
Reflex	326.00	357.10°	-54.60°	Non
Reflex	329.00	2.10°	-54.50°	Non
Reflex	332.00	3.70°	-54.60°	Non
Reflex	335.00	1.90°	-54.50°	Non
Reflex	338.00	1.80°	-54.50°	Non
Reflex	341.00	1.90°	-54.40°	Non
Reflex	344.00	1.80°	-54.40°	Non
Reflex	347.00	1.70°	-54.30°	Non
Reflex	350.00	4.00°	-54.30°	Oui
Reflex	353.00	2.60°	-54.40°	Non
Reflex	356.00	2.90°	-54.40°	Non
Reflex	359.00	4.30°	-54.30°	Oui
Reflex	362.00	2.00°	-54.20°	Non
Reflex	365.00	1.80°	-54.00°	Non
Reflex	368.00	357.00°	-54.20°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	371.00	2.20°	-54.10°	Non
Reflex	374.00	359.40°	-54.10°	Non
Reflex	377.00	2.70°	-54.20°	Non
Reflex	380.00	359.10°	-54.10°	Non
Reflex	383.00	4.60°	-54.10°	Oui
Reflex	386.00	1.70°	-54.00°	Non
Reflex	389.00	3.80°	-54.00°	Non
Reflex	392.00	2.20°	-54.00°	Non
Reflex	395.00	5.00°	-54.00°	Non
Reflex	398.00	5.60°	-54.00°	Non
Reflex	401.00	4.60°	-53.90°	Non
Reflex	404.00	5.80°	-53.90°	Non
Reflex	407.00	4.90°	-53.90°	Non
Reflex	410.00	4.10°	-53.90°	Non
Reflex	413.00	4.00°	-53.80°	Non
Reflex	416.00	3.30°	-53.90°	Non
Reflex	419.00	3.20°	-53.80°	Non
Reflex	422.00	3.40°	-53.80°	Non
Reflex	425.00	3.70°	-53.80°	Non
Reflex	428.00	5.00°	-53.90°	Non
Reflex	431.00	6.30°	-53.80°	Non
Reflex	434.00	2.40°	-53.80°	Oui
Reflex	437.00	5.10°	-53.80°	Non
Reflex	440.00	4.80°	-53.70°	Non
Reflex	443.00	5.50°	-53.70°	Non
Reflex	446.00	4.20°	-53.60°	Non
Reflex	449.00	2.30°	-53.60°	Non
Reflex	452.00	1.00°	-53.70°	Non
Reflex	455.00	3.90°	-53.60°	Non
Reflex	458.00	4.80°	-53.50°	Non
Reflex	461.00	3.20°	-53.60°	Non
Reflex	464.00	4.50°	-53.60°	Non
Reflex	467.00	3.80°	-53.60°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	7.10°	-53.60°	Non					
Reflex	473.00	8.00°	-53.50°	Non					
Reflex	476.00	5.80°	-53.50°	Non					
Reflex	479.00	3.20°	-53.50°	Non					
Reflex	482.00	1.20°	-53.40°	Non					
Reflex	485.00	7.40°	-53.40°	Oui					
Reflex	488.00	148.00°	-53.00°	Oui					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.40	MT <b>Mort-terrain</b>							
2.40	14.00	SY <b>Syénite</b> De couleur rouge, généralement porphyrique avec qq passages dcm trachitiques. La couleur varie du rougeâtre au verdâtre. Plusieurs veules/cheveux de CB recourent la carotte dans rous les sens.							
2.40	14.00	HM30; SR10 <b>Hématisé 30; Séricitique 10</b>	2.40	3.70	D032917	1.30	0.006		0.006
			3.70	5.00	D032918	1.30	0.008		0.008
			5.00	6.50	D032919	1.50	0.011		0.011
			6.50	8.00	D032920	1.50	0.006		0.006
			8.00	9.50	D032921	1.50	0.011		0.011
			9.50	11.00	D032922	1.50	0.021		0.021
			11.00	12.50	D032924	1.50	0.082		0.082
			12.50	14.00	D032925	1.50	0.032		0.032
14.00	140.30	BA <b>Basalte 75°</b> Contact sup. net à 75°AC. Le basalte est fortement séricitisé/(albitisé ?) jusqu'à 28.3 m pour devenir vert. On reconnaît facilement les amygdules ainsi que certaines bordures de coussins après la cote 28m. Le basalte devient plus massif et plus foncé à partir de 56 m. jusqu'à 89 m pour revenir plutôt coussiné par la suite. Intensément séricitisé à partir de 100m	14.00	15.50	D032926	1.50	1.760		1.760
			15.50	17.00	D032927	1.50	0.297		0.297
			17.00	18.50	D032928	1.50	0.009		0.009
			18.50	20.00	D032929	1.50	0.007		0.007
			20.00	21.50	D032930	1.50	0.005		0.005
			21.50	23.00	D032931	1.50	<0.005		0.001
			23.00	24.50	D032932	1.50	0.005		0.005
			24.50	26.00	D032934	1.50	0.005		0.005
			26.00	27.50	D032935	1.50	0.006		0.006
			27.50	29.00	D032936	1.50	0.005		0.005
14.00	28.30	SR75 <b>Séricitique 75</b>							
28.30	62.00	SR10 <b>Séricitique 10</b> Passages dcm séricitiques causés par un réseau de cheveux dont les épontes sont séricitisées	29.00	30.50	D032937	1.50	0.005		0.005
			30.50	32.00	D032938	1.50	0.006		0.006
			32.00	33.50	D032939	1.50	0.005		0.005
			33.50	35.00	D032940	1.50	<0.005		0.001
			35.00	36.50	D032941	1.50	0.005		0.005
			36.50	38.00	D032942	1.50	<0.005		0.001
			38.00	39.50	D032944	1.50	<0.005		0.001



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	39.50	41.00	D032945	1.50	<0.005		0.001	
	41.00	42.50	D032946	1.50	0.005		0.005	
	42.50	44.00	D032947	1.50	0.005		0.005	
	44.00	45.50	D032948	1.50	0.009		0.009	
	45.50	47.00	D032949	1.50	0.006		0.006	
	47.00	48.50	D032950	1.50	0.005		0.005	
	48.50	50.00	D032952	1.50	0.005		0.005	
	50.00	51.50	D032954	1.50	0.005		0.005	
	51.50	53.00	D032955	1.50	<0.005		0.001	
	53.00	54.50	D032956	1.50	0.009		0.009	
	54.50	56.00	D032957	1.50	<0.005		0.001	
	56.00	57.50	D032958	1.50	0.007		0.007	
	57.50	59.00	D032959	1.50	<0.005		0.001	
	59.00	60.50	D032960	1.50	0.013		0.013	
	60.50	62.00	D032961	1.50	0.021		0.021	
62.00	95.00	SR60	62.00	63.50	D032962	1.50	<0.005	0.001
		<b>Séricitique 60</b>	63.50	65.00	D032964	1.50	<0.005	0.001
			65.00	66.50	D032965	1.50	<0.005	0.001
			66.50	68.00	D032966	1.50	<0.005	0.001
			68.00	69.50	D032967	1.50	<0.005	0.001
			69.50	71.00	D032968	1.50	<0.005	0.001
			71.00	72.50	D032969	1.50	<0.005	0.001
			72.50	74.00	D032970	1.50	<0.005	0.001
			74.00	75.50	D032971	1.50	0.005	0.005
			75.50	77.00	D032972	1.50	<0.005	0.001
			77.00	78.50	D032974	1.50	<0.005	0.001
			78.50	80.00	D032975	1.50	<0.005	0.001
			80.00	81.50	D032976	1.50	<0.005	0.001
			81.50	83.00	D032977	1.50	<0.005	0.001
			83.00	84.50	D032978	1.50	<0.005	0.001
			84.50	86.00	D032979	1.50	<0.005	0.001
			86.00	87.50	D032980	1.50	<0.005	0.001
			87.50	89.00	D032981	1.50	0.008	0.008

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
95.00	100.80	HM40 Hématisé 40	89.00	90.50	D032982	1.50	<0.005		0.001
			90.50	92.00	D032984	1.50	<0.005		0.001
			92.00	93.50	D032985	1.50	<0.005		0.001
			93.50	95.00	D032986	1.50	<0.005		0.001
			95.00	96.50	D032987	1.50	0.163		0.163
			96.50	98.00	D032988	1.50	0.335		0.335
			98.00	99.50	D032989	1.50	0.121		0.121
			99.50	101.00	D032990	1.50	<0.005		0.001
			100.80	140.30	SR50 Séricitique 50	101.00	102.50	D032992	1.50
102.50	104.00	D032994				1.50	<0.005		0.001
104.00	105.50	D032995				1.50	<0.005		0.001
105.50	107.00	D032996				1.50	<0.005		0.001
107.00	108.50	D032997				1.50	<0.005		0.001
108.50	110.00	D032998				1.50	<0.005		0.001
110.00	111.50	D032999				1.50	<0.005		0.001
111.50	113.00	D033000				1.50	<0.005		0.001
113.00	114.50	D033001				1.50	<0.005		0.001
114.50	116.00	D033002				1.50	<0.005		0.001
116.00	117.50	D033004				1.50	0.005		0.005
117.50	119.00	D033005				1.50	<0.005		0.001
119.00	120.50	D033006				1.50	<0.005		0.001
120.50	122.00	D033007				1.50	<0.005		0.001
122.00	123.50	D033008				1.50	<0.005		0.001
123.50	125.00	D033009				1.50	<0.005		0.001
125.00	126.50	D033010				1.50	<0.005		0.001
126.50	128.00	D033011				1.50	<0.005		0.001
128.00	129.50	D033012				1.50	<0.005		0.001
129.50	131.00	D033014	1.50	<0.005		0.001			
131.00	132.50	D033015	1.50	0.059		0.059			
132.50	134.00	D033016	1.50	<0.005		0.001			
134.00	135.50	D033017	1.50	<0.005		0.001			
135.50	137.00	D033018	1.50	<0.005		0.001			
137.00	138.65	D033019	1.65	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
140.30	148.85	RY <b>Rhyolite 35°</b> Roche à très haut contenu en silice avec des fantômes de sphérulites carbonatées. La matrice est constitué d'au moins 80% Silice avec jusqu'à 15% de Py extrêmement fine. Certains appellent cette roche un basalte remplacé. La présence de sphérulites la qualifie plutôt de rhyolite.	138.65	140.30	D033020	1.65	<0.005		0.001
			140.30	141.50	D033021	1.20	0.006		0.006
			141.50	143.00	D033022	1.50	0.014		0.014
			143.00	144.50	D033024	1.50	0.006		0.006
			144.50	146.00	D033025	1.50	0.018		0.018
			146.00	147.50	D033026	1.50	0.611		0.611
			147.50	148.85	D033027	1.35	0.012		0.012
148.30	330.40	HM40 <b>Hématisé 40</b>							
148.85	406.20	SY; POR <b>Syénite 40°; Porphyrique</b> De couleur rouge typique à Po de Fp grossiers prismatiques. Les Po sont zonés. La roche est recoupée par de nombreuses veinules de CB selon 2 système perp. l'un par rapport à l'autre, l'un à 65°AC et l'autre mieux développé à 35°AC. Elle devient sanguine ("PLUM") à partir de 252.5m	148.85	150.50	D033028	1.65	<0.005		0.001
			150.50	152.00	D033029	1.50	0.028		0.028
			152.00	153.50	D033030	1.50	0.006		0.006
			153.50	155.00	D033032	1.50	<0.005		0.001
			155.00	156.50	D033034	1.50	<0.005		0.001
			156.50	158.00	D033035	1.50	0.013		0.013
			158.00	159.50	D033036	1.50	<0.005		0.001
			159.50	161.00	D033037	1.50	0.031		0.031
			161.00	162.50	D033038	1.50	0.013		0.013
			162.50	164.00	D033039	1.50	0.030		0.030
			164.00	165.50	D033040	1.50	0.019		0.019
			165.50	167.00	D033041	1.50	0.010		0.010
			167.00	168.50	D033042	1.50	0.011		0.011
			168.50	170.00	D033044	1.50	0.013		0.013
			170.00	171.50	D033045	1.50	0.007		0.007
			171.50	173.00	D033046	1.50	0.011		0.011
			173.00	174.50	D033047	1.50	0.028		0.028
			174.50	176.00	D033048	1.50	0.021		0.021
176.00	177.50	D033049	1.50	0.051		0.051			
177.50	179.00	D033050	1.50	1.865		1.865			
179.00	180.50	D033051	1.50	0.050		0.050			
180.50	182.00	D033052	1.50	0.269		0.269			
182.00	183.50	D033054	1.50	0.357		0.357			
183.50	185.00	D033055	1.50	0.033		0.033			

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				185.00	186.50	D033056	1.50	0.179		0.179
				186.50	188.00	D033057	1.50	0.250		0.250
				188.00	189.50	D033058	1.50	0.265		0.265
				189.50	191.00	D033059	1.50	0.590		0.590
				191.00	192.50	D033060	1.50	0.043		0.043
				192.50	194.00	D033061	1.50	0.850		0.850
				194.00	195.50	D033062	1.50	0.027		0.027
				195.50	197.00	D033064	1.50	0.499		0.499
				197.00	198.50	D033065	1.50	0.368		0.368
				198.50	200.00	D033066	1.50	0.140		0.140
				200.00	201.50	D033067	1.50	0.162		0.162
				201.50	203.00	D033068	1.50	0.211		0.211
				203.00	204.50	D033069	1.50	0.181		0.181
				204.50	206.00	D033070	1.50	0.346		0.346
				206.00	207.50	D033072	1.50	0.211		0.211
				207.50	209.00	D033074	1.50	0.086		0.086
				209.00	210.50	D033075	1.50	0.201		0.201
				210.50	212.00	D033076	1.50	0.400		0.400
				212.00	213.50	D033077	1.50	0.410		0.410
				213.50	215.00	D033078	1.50	0.064		0.064
214.50	217.50	CAT; FAI; FRC		215.00	216.50	D033079	1.50	0.009		0.009
		<b>Cataclasé; Faille; Fracturé</b>		216.50	218.00	D033080	1.50	0.470		0.470
				218.00	219.50	D033081	1.50	0.049		0.049
				219.50	221.00	D033082	1.50	0.108		0.108
				221.00	222.50	D033084	1.50	0.037		0.037
				222.50	224.00	D033085	1.50	0.025		0.025
				224.00	225.50	D033086	1.50	0.047		0.047
				225.50	227.00	D033087	1.50	0.006		0.006
				227.00	228.50	D033088	1.50	0.045		0.045
				228.50	230.00	D033089	1.50	0.035		0.035
				230.00	231.50	D033090	1.50	0.045		0.045
				231.50	233.00	D033091	1.50	0.007		0.007
				233.00	234.50	D033092	1.50	0.174		0.174

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
241.10	243.50	CAT; FRC; CIS <b>Cataclasé; Fracturé; Cisaillement</b> Syénite bréchifiée avec 2% de Py	234.50	236.00	D033094	1.50	0.115		0.115
			236.00	237.50	D033095	1.50	0.173		0.173
			237.50	239.00	D033096	1.50	0.294		0.294
			239.00	240.00	D033097	1.00	0.133		0.133
			240.00	241.10	D033098	1.10	0.710		0.710
			241.10	242.00	D033099	0.90	3.910		3.910
			242.00	243.50	D033100	1.50	5.850		5.850
			243.50	245.00	D033101	1.50	0.118		0.118
			245.00	246.50	D033102	1.50	0.009		0.009
			246.50	248.00	D033104	1.50	0.005		0.005
			248.00	249.50	D033105	1.50	0.236		0.236
			249.50	251.00	D033106	1.50	<0.005		0.001
			251.00	252.50	D033107	1.50	0.005		0.005
			252.50	254.00	D033108	1.50	<0.005		0.001
			254.00	255.50	D033109	1.50	0.007		0.007
			255.50	257.00	D033110	1.50	0.008		0.008
			257.00	258.50	D033112	1.50	0.016		0.016
258.50	260.00	D033114	1.50	<0.005		0.001			
260.00	261.50	D033115	1.50	0.008		0.008			
261.50	262.20	D033116	0.70	0.005		0.005			
262.20	267.10	CIS <b>Cisaillement 45°</b> Syénite cisailée et chloritisée avec 1-2% de Py disséminée	262.20	263.00	D033117	0.80	0.084		0.084
			263.00	264.50	D033118	1.50	0.005		0.005
			264.50	266.00	D033119	1.50	0.103		0.103
			266.00	267.10	D033120	1.10	0.006		0.006
			267.10	268.05	D033121	0.95	0.018		0.018
			268.05	269.00	D033122	0.95	0.032		0.032
			269.00	270.50	D033124	1.50	0.068		0.068
			270.50	272.00	D033125	1.50	0.032		0.032
			272.00	273.50	D033126	1.50	0.050		0.050
			273.50	275.00	D033127	1.50	0.033		0.033
			275.00	276.50	D033128	1.50	0.012		0.012
			276.50	278.00	D033129	1.50	0.026		0.026
			278.00	279.50	D033130	1.50	0.019		0.019

Corporation Minière Osisko Div. Exploration

Description				Analyse						
				De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
				279.50	281.00	D033131	1.50	0.010		0.010
				281.00	282.50	D033132	1.50	0.047		0.047
				282.50	284.00	D033134	1.50	0.013		0.013
				284.00	285.50	D033135	1.50	0.031		0.031
				285.50	287.00	D033136	1.50	0.042		0.042
				287.00	288.50	D033137	1.50	0.005		0.005
				288.50	290.00	D033138	1.50	<0.005		0.001
				290.00	291.50	D033139	1.50	<0.005		0.001
				291.50	293.00	D033140	1.50	0.009		0.009
				293.00	294.50	D033141	1.50	0.067		0.067
				294.50	296.00	D033142	1.50	0.024		0.024
				296.00	297.50	D033144	1.50	<0.005		0.001
				297.50	298.50	D033145	1.00	0.059		0.059
				298.50	299.50	D033146	1.00	0.221		0.221
299.50	307.20	CAT; FRC <b>Cataclasé; Fracturé</b>		299.50	300.50	D033147	1.00	0.873		0.873
				300.50	302.00	D033148	1.50	1.150		1.150
				302.00	303.50	D033149	1.50	1.450		1.450
				303.50	305.00	D033150	1.50	0.201		0.201
				305.00	306.00	D033152	1.00	0.519		0.519
				306.00	307.20	D033154	1.20	1.965		1.965
307.20	309.20	CIS <b>Cisaillement 60°</b>		307.20	308.20	D033155	1.00	0.038		0.038
				308.20	309.20	D033156	1.00	0.031		0.031
				309.20	310.90	D033157	1.70	0.038		0.038
				310.90	312.50	D033158	1.60	<0.005		0.001
				312.50	314.00	D033159	1.50	0.224		0.224
				314.00	315.50	D033160	1.50	0.005		0.005
				315.50	317.20	D033161	1.70	0.012		0.012
				317.20	318.50	D033162	1.30	0.006		0.006
318.50	320.00	FAI; FRC <b>Faille 35°; Fracturé</b> Plusieurs plans montrant de la boue de faille		318.50	320.00	D033164	1.50	0.030		0.030
				320.00	321.50	D033165	1.50	0.005		0.005
				321.50	323.00	D033166	1.50	0.010		0.010
				323.00	324.50	D033167	1.50	<0.005		0.001
				324.50	326.00	D033168	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
330.40	342.90	CH30; SR20; HM20; SI20 <b>Chloriteux 30; Séricitique 20; Hématisé 20; Silicifié 20</b> Zone de déformation montrant un cisaillement modéré à intense à 55°AC. La syénite cisailée est fortement altérée, injectée par des passages cm à dcm de matériel mafique, ainsi que par des filons de qtz fumé // au cisaillement. Certains passages dcm montrent également une bréchification modérée.	326.00	327.50	D033169	1.50	0.005		0.005
			327.50	329.00	D033170	1.50	0.008		0.008
			329.00	330.40	D033171	1.40	0.005		0.005
330.40	342.90	CIS <b>Cisaillement 45°</b>	330.40	332.00	D033172	1.60	0.033		0.033
			332.00	333.50	D033174	1.50	0.684		0.684
			333.50	335.00	D033175	1.50	0.393		0.393
			335.00	336.50	D033176	1.50	0.043		0.043
			336.50	338.00	D033177	1.50	0.201		0.201
			338.00	339.50	D033178	1.50	<0.005		0.001
			339.50	341.20	D033179	1.70	0.016		0.016
			341.20	342.90	D033180	1.70	0.018		0.018
342.90	446.10	HM25 <b>Hématisé 25</b>	342.90	344.00	D033181	1.10	0.029		0.029
			344.00	345.50	D033182	1.50	<0.005		0.001
			345.50	347.00	D033184	1.50	<0.005		0.001
			347.00	348.50	D033185	1.50	<0.005		0.001
			348.50	350.00	D033186	1.50	0.012		0.012
			350.00	351.50	D033187	1.50	0.020		0.020
			351.50	353.00	D033188	1.50	0.352		0.352
			353.00	354.50	D033189	1.50	0.247		0.247
			354.50	356.00	D033190	1.50	0.524		0.524
			356.00	357.50	D033192	1.50	0.005		0.005
			357.50	359.00	D033194	1.50	0.045		0.045
			359.00	360.00	D033195	1.00	0.093		0.093
361.20	369.20	SY; QZVN <b>Syénite; Veine de Quartz massive</b> Syénite hématisée envahie par plusieurs veinules/veines de Qtz-CB de 1-3 cm d'ép. à 70°AC et 35 °AC et qq unes + ou - // à	360.00	361.20	D033196	1.20	<0.005		0.001
			361.20	362.00	D033197	0.80	<0.005		0.001
			362.00	363.50	D033198	1.50	0.018		0.018
			363.50	365.00	D033199	1.50	0.019		0.019

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
AC. Représente peut-être un couloir de déformation. Le % de Py reste très faible, en tr.	365.00	366.50	D033200	1.50	0.015		0.015
	366.50	368.00	D033201	1.50	<0.005		0.001
	368.00	369.20	D033202	1.20	<0.005		0.001
	369.20	370.90	D033204	1.70	0.114		0.114
	370.90	372.50	D033205	1.60	0.007		0.007
	372.50	374.00	D033206	1.50	0.012		0.012
	374.00	375.50	D033207	1.50	0.007		0.007
	375.50	377.00	D033208	1.50	0.012		0.012
	377.00	378.50	D033209	1.50	<0.005		0.001
	378.50	380.00	D033210	1.50	0.503		0.503
	380.00	381.50	D033211	1.50	0.063		0.063
	381.50	383.00	D033212	1.50	0.006		0.006
	383.00	384.50	D033214	1.50	0.007		0.007
	384.50	386.00	D033215	1.50	0.006		0.006
	386.00	387.50	D033216	1.50	0.100		0.100
	387.50	389.00	D033217	1.50	0.846		0.846
	389.00	390.50	D033218	1.50	0.023		0.023
	390.50	392.00	D033219	1.50	0.013		0.013
	392.00	393.50	D033220	1.50	<0.005		0.001
	393.50	395.00	D033221	1.50	<0.005		0.001
	395.00	396.50	D033222	1.50	<0.005		0.001
	396.50	398.00	D033224	1.50	0.005		0.005
	398.00	399.50	D033225	1.50	0.007		0.007
	399.50	401.00	D033226	1.50	<0.005		0.001
	401.00	402.50	D033227	1.50	0.012		0.012
	402.50	404.00	D033228	1.50	0.015		0.015
	404.00	405.50	D033229	1.50	0.010		0.010
405.50	407.00	D033230	1.50	0.012		0.012	
407.00	408.50	D033232	1.50	0.005		0.005	
408.50	410.00	D033234	1.50	0.040		0.040	
410.00	411.50	D033235	1.50	0.019		0.019	
411.50	413.00	D033236	1.50	0.042		0.042	
413.00	414.50	D033237	1.50	0.032		0.032	
406.20      490.30      SY <b>Syérite</b> Id. à la précédente mais les Po de Fp sont à peu près inexistantes. Les derniers 6.9m sont fortement séricitisés. Fin du trou à 490.3m.							



Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			414.50	416.00	D033238	1.50		0.008		0.008
			416.00	417.50	D033239	1.50		0.013		0.013
			417.50	419.00	D033240	1.50		0.099		0.099
			419.00	420.50	D033241	1.50		0.008		0.008
			420.50	422.00	D033242	1.50		0.017		0.017
			422.00	423.50	D033244	1.50		0.021		0.021
			423.50	425.00	D033245	1.50		0.013		0.013
			425.00	426.50	D033246	1.50		<0.005		0.001
			426.50	428.00	D033247	1.50		<0.005		0.001
			428.00	429.50	D033248	1.50		<0.005		0.001
			429.50	431.00	D033249	1.50		0.013		0.013
			431.00	432.50	D033250	1.50		<0.005		0.001
			432.50	434.00	D033251	1.50		<0.005		0.001
			434.00	435.50	D033252	1.50		0.767		0.767
			435.50	437.00	D033254	1.50		0.803		0.803
			437.00	438.50	D033255	1.50		0.048		0.048
			438.50	440.00	D033256	1.50		<0.005		0.001
			440.00	441.50	D033257	1.50		<0.005		0.001
			441.50	443.00	D033258	1.50		0.011		0.011
			443.00	444.50	D033259	1.50		0.008		0.008
			444.50	446.10	D033260	1.60		0.139		0.139
446.10	454.90	CB40	446.10	447.50	D033262	1.40		0.233		0.233
		<b>Carbonaté 40</b>	447.50	449.00	D033264	1.50		0.043		0.043
		La carbonatation est dominante par rapport à l'hématitisation.	449.00	450.50	D033265	1.50		0.406		0.406
			450.50	452.00	D033266	1.50		0.341		0.341
			452.00	453.50	D033267	1.50		0.551		0.551
			453.50	454.90	D033268	1.40		0.095		0.095
454.90	477.40	HM50	454.90	456.50	D033269	1.60		0.435		0.435
		<b>Hématisé 50</b>	456.50	458.00	D033270	1.50		0.210		0.210
			458.00	459.50	D033272	1.50		0.314		0.314
			459.50	461.00	D033274	1.50		0.796		0.796
			461.00	462.50	D033275	1.50		0.657		0.657
			462.50	464.00	D033276	1.50		1.170		1.170

Corporation Minière Osisko Div. Exploration

Description			Analyse							
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
			464.00	465.50	D033277	1.50	1.675		1.675	
			465.50	467.00	D033278	1.50	2.250		2.250	
			467.00	468.50	D033279	1.50	0.123		0.123	
			468.50	470.00	D033280	1.50	0.198		0.198	
			470.00	471.50	D033281	1.50	0.253		0.253	
			471.50	473.00	D033282	1.50	0.123		0.123	
			473.00	474.50	D033284	1.50	0.172		0.172	
			474.50	476.00	D033285	1.50	0.044		0.044	
			476.00	477.40	D033286	1.40	0.157		0.157	
477.40	478.00	IM <b>Intrusion mafique (dyke) 70°</b> Probablement zone de cisaillement introduite par un dyke de composition mafique. Accompagnée par des injections de Qz-CB de forme très irrégulière.								
477.40	478.00	CH50 <b>Chloriteux 50</b>	477.40	479.00	D033287	1.60	0.194		0.194	
478.00	483.45	RE60 <b>Remplacé (forte silicification) 60</b>	479.00	480.50	D033288	1.50	0.124		0.124	
			480.50	482.00	D033289	1.50	0.179		0.179	
			482.00	483.45	D033290	1.45	0.217		0.217	
483.45	490.30	SR40 <b>Séricitique 40</b>	483.45	485.00	D033291	1.55	0.183		0.183	
			485.00	486.50	D033292	1.50	0.632		0.632	
			486.50	488.00	D033294	1.50	0.795		0.795	
			488.00	489.50	D033295	1.50	0.361		0.361	
			489.50	490.30	D033296	0.80	0.316		0.316	
490.30	Fin du sondage Nombre d'échantillons : 332 Nombre d'échantillons QAQC : 48 Longueur totale échantillonnée : 487.90									

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
9.50	11.00	D032923	D032922	1.50	0.023	0.023
23.00	23.00	D032933	J	0.00	0.721	0.721
36.50	38.00	D032943	D032942	1.50	<0.005	0.001
47.00	47.00	D032951	M1	0.00	<0.005	0.001
48.50	48.50	D032953	K	0.00	1.055	1.055
62.00	63.50	D032963	D032962	1.50	<0.005	0.001
75.50	75.50	D032973	L	0.00	2.210	2.210
89.00	90.50	D032983	D032982	1.50	<0.005	0.001
99.50	99.50	D032991	M1	0.00	<0.005	0.001
101.00	101.00	D032993	M	0.00	3.080	3.080
114.50	116.00	D033003	D033002	1.50	<0.005	0.001
128.00	128.00	D033013	J	0.00	0.709	0.709
141.50	143.00	D033023	D033022	1.50	0.009	0.009
152.00	152.00	D033031	M1	0.00	<0.005	0.001
153.50	153.50	D033033	K	0.00	1.015	1.015
167.00	168.50	D033043	D033042	1.50	0.011	0.011
180.50	180.50	D033053	L	0.00	2.240	2.240
194.00	195.50	D033063	D033062	1.50	0.029	0.029
204.50	204.50	D033071	M1	0.00	<0.005	0.001
206.00	206.00	D033073	M	0.00	3.000	3.000
219.50	221.00	D033083	D033082	1.50	0.094	0.094
233.00	233.00	D033093	J	0.00	0.766	0.766
245.00	246.50	D033103	D033102	1.50	<0.005	0.001
255.50	255.50	D033111	M1	0.00	<0.005	0.001
257.00	257.00	D033113	K	0.00	1.065	1.065
268.05	269.00	D033123	D033122	0.95	0.029	0.029
281.00	281.00	D033133	L	0.00	2.320	2.320
294.50	296.00	D033143	D033142	1.50	0.024	0.024
303.50	303.50	D033151	M1	0.00	0.016	0.016
305.00	305.00	D033153	M	0.00	3.320	3.320
317.20	318.50	D033163	D033162	1.30	0.009	0.009
330.40	330.40	D033173	J	0.00	0.666	0.666
344.00	345.50	D033183	D033182	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
354.50	354.50	D033191	M1	0.00	<0.005	0.001
356.00	356.00	D033193	K	0.00	1.045	1.045
368.00	369.20	D033203	D033202	1.20	0.008	0.008
381.50	381.50	D033213	L	0.00	2.130	2.130
395.00	396.50	D033223	D033222	1.50	<0.005	0.001
405.50	405.50	D033231	M1	0.00	<0.005	0.001
407.00	407.00	D033233	M	0.00	3.130	3.130
420.50	422.00	D033243	D033242	1.50	0.032	0.032
434.00	434.00	D033253	J	0.00	0.915	0.915
444.50	444.50	D033261	M1	0.00	<0.005	0.001
446.10	447.50	D033263	D033262	1.40	0.251	0.251
456.50	456.50	D033271	M1	0.00	<0.005	0.001
458.00	458.00	D033273	K	0.00	1.065	1.065
471.50	473.00	D033283	D033282	1.50	0.112	0.112
485.00	485.00	D033293	L	0.00	2.120	2.120



Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.40°	-58.50°	Non
Reflex	77.00	0.40°	-58.40°	Non
Reflex	80.00	0.70°	-58.40°	Non
Reflex	83.00	0.70°	-58.30°	Non
Reflex	86.00	0.90°	-58.20°	Non
Reflex	89.00	1.00°	-58.20°	Non
Reflex	92.00	1.40°	-58.10°	Non
Reflex	95.00	1.20°	-58.00°	Non
Reflex	98.00	1.60°	-57.90°	Non
Reflex	101.00	1.60°	-57.90°	Non
Reflex	104.00	1.70°	-57.70°	Non
Reflex	107.00	1.90°	-57.80°	Non
Reflex	110.00	2.10°	-57.80°	Non
Reflex	113.00	2.30°	-57.80°	Non
Reflex	116.00	2.50°	-57.80°	Non
Reflex	119.00	2.60°	-57.80°	Non
Reflex	122.00	2.80°	-57.80°	Non
Reflex	125.00	3.10°	-57.90°	Non
Reflex	128.00	3.50°	-57.90°	Non
Reflex	131.00	3.30°	-58.00°	Non
Reflex	134.00	3.60°	-57.90°	Non
Reflex	137.00	3.70°	-57.90°	Non
Reflex	140.00	4.20°	-58.00°	Non
Reflex	143.00	4.20°	-57.90°	Non
Reflex	146.00	4.70°	-58.00°	Non
Reflex	149.00	4.60°	-58.00°	Non
Reflex	152.00	4.60°	-58.00°	Non
Reflex	155.00	4.90°	-58.00°	Non
Reflex	158.00	5.00°	-57.90°	Non
Reflex	161.00	5.20°	-58.00°	Non
Reflex	164.00	5.20°	-58.00°	Non
Reflex	167.00	5.50°	-58.00°	Non
Reflex	170.00	5.60°	-58.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	5.40°	-58.10°	Non
Reflex	176.00	5.70°	-58.10°	Non
Reflex	179.00	5.90°	-58.10°	Non
Reflex	182.00	6.00°	-58.10°	Non
Reflex	185.00	6.10°	-58.00°	Non
Reflex	188.00	6.30°	-58.10°	Non
Reflex	191.00	6.30°	-58.00°	Non
Reflex	194.00	6.50°	-58.00°	Non
Reflex	197.00	6.60°	-58.00°	Non
Reflex	200.00	6.70°	-58.00°	Non
Reflex	203.00	6.70°	-57.90°	Non
Reflex	206.00	6.90°	-57.90°	Non
Reflex	209.00	7.20°	-57.90°	Non
Reflex	212.00	7.20°	-57.90°	Non
Reflex	215.00	7.20°	-57.90°	Non
Reflex	218.00	7.20°	-57.90°	Non
Reflex	221.00	6.80°	-57.90°	Non
Reflex	224.00	6.80°	-57.90°	Non
Reflex	227.00	6.90°	-57.90°	Non
Reflex	230.00	7.60°	-57.90°	Non
Reflex	233.00	7.40°	-57.90°	Non
Reflex	236.00	6.80°	-57.90°	Non
Reflex	239.00	8.10°	-57.90°	Non
Reflex	242.00	7.30°	-57.90°	Non
Reflex	245.00	9.30°	-57.90°	Oui
Reflex	248.00	7.00°	-57.90°	Non
Reflex	251.00	8.80°	-57.90°	Non
Reflex	254.00	8.80°	-57.90°	Non
Reflex	257.00	8.80°	-57.90°	Non
Reflex	260.00	8.60°	-57.90°	Non
Reflex	263.00	8.80°	-57.90°	Non
Reflex	266.00	8.40°	-57.90°	Non
Reflex	269.00	8.70°	-57.90°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	10.10°	-57.90°	Non	Reflex	371.00	12.90°	-57.10°	Non
Reflex	275.00	9.80°	-57.90°	Non	Reflex	374.00	12.20°	-57.10°	Non
Reflex	278.00	10.70°	-57.90°	Non	Reflex	377.00	12.30°	-57.10°	Non
Reflex	281.00	9.30°	-57.90°	Non	Reflex	380.00	13.80°	-57.10°	Non
Reflex	284.00	7.80°	-57.90°	Non	Reflex	383.00	13.20°	-57.00°	Non
Reflex	287.00	8.00°	-57.90°	Non	Reflex	386.00	8.80°	-57.00°	Oui
Reflex	290.00	7.90°	-57.90°	Non	Reflex	389.00	13.80°	-57.00°	Non
Reflex	293.00	7.30°	-57.80°	Non	Reflex	392.00	14.10°	-56.90°	Non
Reflex	296.00	5.60°	-57.80°	Non	Reflex	395.00	13.90°	-56.90°	Non
Reflex	299.00	6.90°	-57.80°	Non	Reflex	398.00	9.10°	-56.90°	Oui
Reflex	302.00	6.10°	-57.50°	Non	Reflex	401.00	14.70°	-56.90°	Non
Reflex	305.00	7.00°	-57.20°	Non	Reflex	404.00	13.30°	-56.90°	Non
Reflex	308.00	10.10°	-57.30°	Non	Reflex	407.00	14.80°	-56.90°	Non
Reflex	311.00	9.90°	-57.30°	Non	Reflex	410.00	15.80°	-56.90°	Non
Reflex	314.00	10.70°	-57.30°	Non	Reflex	413.00	16.10°	-56.80°	Non
Reflex	317.00	10.60°	-57.30°	Non	Reflex	416.00	14.10°	-56.80°	Non
Reflex	320.00	11.80°	-57.30°	Non	Reflex	419.00	8.60°	-56.80°	Oui
Reflex	323.00	11.90°	-57.30°	Non	Reflex	422.00	11.00°	-56.70°	Non
Reflex	326.00	10.60°	-57.30°	Non	Reflex	425.00	12.30°	-56.70°	Non
Reflex	329.00	11.00°	-57.30°	Non	Reflex	428.00	15.20°	-56.70°	Non
Reflex	332.00	12.40°	-57.30°	Non	Reflex	431.00	9.20°	-56.70°	Oui
Reflex	335.00	12.50°	-57.30°	Non	Reflex	434.00	13.10°	-56.70°	Non
Reflex	338.00	12.70°	-57.30°	Non	Reflex	437.00	15.60°	-56.70°	Non
Reflex	341.00	11.00°	-57.30°	Non	Reflex	440.00	14.70°	-56.70°	Non
Reflex	344.00	12.90°	-57.40°	Non	Reflex	443.00	15.10°	-56.70°	Non
Reflex	347.00	12.30°	-57.40°	Non	Reflex	446.00	15.60°	-56.70°	Non
Reflex	350.00	12.90°	-57.40°	Non	Reflex	449.00	16.60°	-56.80°	Non
Reflex	353.00	11.70°	-57.40°	Non	Reflex	452.00	15.30°	-56.70°	Non
Reflex	356.00	10.20°	-57.30°	Oui	Reflex	455.00	16.60°	-56.70°	Non
Reflex	359.00	12.20°	-57.40°	Non	Reflex	458.00	17.20°	-56.70°	Non
Reflex	362.00	13.10°	-57.20°	Non	Reflex	461.00	13.40°	-56.60°	Oui
Reflex	365.00	11.80°	-57.10°	Non	Reflex	464.00	8.90°	-56.60°	Oui
Reflex	368.00	11.60°	-57.10°	Non	Reflex	467.00	15.50°	-56.50°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	470.00	17.90°	-56.40°	Non					
Reflex	473.00	17.40°	-56.30°	Non					
Reflex	476.00	18.60°	-56.20°	Non					
Reflex	479.00	18.40°	-56.10°	Non					
Reflex	482.00	18.50°	-56.00°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	2.70	MT <b>Mort-terrain</b> 0							
2.70	17.90	BA; AMY <b>Basalte; Amygdalaire</b> massive aphanitique, passage cisailé, amygdules de QZ et carbonâtes, CL+++ , BO++ , HM+ , SR+ , PY fine diss	2.70	4.00	D029460	1.30	0.006		0.006
3.40	3.70	FRC <b>Fracturé 50°</b> fragments cm et boue verdâtre	4.00	5.50	D029461	1.50	0.005		0.005
			5.50	7.00	D029462	1.50	0.005		0.005
			7.00	8.50	D029463	1.50	<0.005		0.001
			8.50	10.00	D029464	1.50	<0.005		0.001
			10.00	11.50	D029465	1.50	0.007		0.007
			11.50	13.00	D029466	1.50	0.006		0.006
			13.00	14.50	D029467	1.50	<0.005		0.001
			14.50	16.00	D029468	1.50	0.071		0.071
			16.00	17.00	D029470	1.00	2.870		2.870
			17.00	17.90	D029471	0.90	0.017		0.017
17.90	25.20	SY; MAS; FIN <b>Syénite 70°; Roche massive; Grains fins</b> grenue, localement phénocristaux sub arrondi, altération en calcite, hématisation, localement séricitisé, PY fine diss	17.90	19.50	D029472	1.60	0.012		0.012
			19.50	21.00	D029473	1.50	0.010		0.010
21.00	22.00	SI03; CB04; SR02; HM01 <b>Silicifié 3; Carbonaté 4; Séricitique 2; Hématisé 1</b> PY ± 1%	21.00	22.50	D029474	1.50	0.097		0.097
			22.50	24.00	D029475	1.50	0.006		0.006
			24.00	25.20	D029476	1.20	0.006		0.006
25.20	27.70	BA; AMY; APH; MAS <b>Basalte 40°; Amygdalaire; Aphanitique; Roche massive</b> massive aphanitique, légèrement cisailé, CL+++ , calcite, PY fine irrég diss	25.20	26.70	D029477	1.50	<0.005		0.001
			26.70	27.70	D029478	1.00	<0.005		0.001
27.70	28.70	GA; MAS; FIN <b>Gabbro 50°; Roche massive; Grains fins</b> grenue, altération en calcite séricite et chlorite, légère séricitisation, PY irrég diss	27.70	28.70	D029480	1.00	<0.005		0.001
28.70	87.00	BA; MAS; AMY; APH <b>Basalte 50°; Roche massive; Amygdalaire; Aphanitique</b> massive aphanitique, amygdalaire lentille de QZ hématisé , altération en calcite, chloritisation, passage fortement séricitisé, oxydes de carbonâtes, PY irrég diss	28.70	30.00	D029481	1.30	<0.005		0.001
			30.00	31.50	D029482	1.50	<0.005		0.001
			31.50	33.00	D029483	1.50	<0.005		0.001
			33.00	34.50	D029484	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
52.50	87.00	SR05; CH02; HM01 <b>Séricitique 5; Chloriteux 2; Hématisé 1</b>	34.50	36.00	D029485	1.50	<0.005		0.001
			36.00	37.50	D029486	1.50	<0.005		0.001
			37.50	39.00	D029487	1.50	<0.005		0.001
			39.00	40.50	D029488	1.50	<0.005		0.001
			40.50	42.00	D029490	1.50	<0.005		0.001
			42.00	43.50	D029491	1.50	<0.005		0.001
			43.50	45.00	D029492	1.50	<0.005		0.001
			45.00	46.50	D029493	1.50	0.014		0.014
			46.50	48.00	D029494	1.50	0.006		0.006
			48.00	49.50	D029495	1.50	0.007		0.007
			49.50	51.00	D029497	1.50	<0.005		0.001
			51.00	52.50	D029498	1.50	<0.005		0.001
			52.50	54.00	D029500	1.50	<0.005		0.001
			54.00	55.50	D029501	1.50	<0.005		0.001
			55.50	57.00	D029502	1.50	<0.005		0.001
			57.00	58.50	D029503	1.50	0.087		0.087
			58.50	60.00	D029504	1.50	0.006		0.006
			60.00	61.50	D029505	1.50	0.005		0.005
			61.50	63.00	D029506	1.50	<0.005		0.001
			63.00	64.50	D029507	1.50	<0.005		0.001
64.50	66.00	D029508	1.50	0.007		0.007			
66.00	67.50	D029510	1.50	0.007		0.007			
67.50	69.00	D029511	1.50	<0.005		0.001			
69.00	70.50	D029512	1.50	0.008		0.008			
70.50	72.00	D029513	1.50	0.005		0.005			
71.70	71.90	FRC <b>Fracturé</b> fragments cm, oxydes de carbonâte calcite	72.00	73.50	D029514	1.50	0.021		0.021
			73.50	75.00	D029515	1.50	0.013		0.013
			75.00	76.50	D029516	1.50	0.007		0.007
			76.50	78.00	D029517	1.50	0.006		0.006
			78.00	79.50	D029518	1.50	1.415		1.415
			79.50	81.00	D029520	1.50	0.360		0.360
			81.00	82.50	D029521	1.50	0.340		0.340
80.90	81.00	FRC <b>Fracturé 40°</b> fragments ocre à oxydes de carbonâtes	81.00	82.50	D029521	1.50	0.340		0.340

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
82.10	82.20	FRC <b>Fracturé 70°</b>	82.50	84.00	D029522	1.50	0.160		0.160
			84.00	85.50	D029523	1.50	0.071		0.071
			85.50	87.00	D029524	1.50	0.015		0.015
86.00	86.30	FRC <b>Fracturé 50°</b>							
87.00	475.90	SY; MAS; FIN; MTY <b>Syénite 50°; Roche massive; Grains fins; Grains moyens</b> grenue, localement, phénocristaux de FP, légèrement hématisé, passage fortement séricitisé, localement altéré en calcite, veinules de QZ carbonaté, HM+++, SR+, CL++, leucoxène, localement magnétique, PY automorphe et fine irrég diss	87.00	88.50	D029525	1.50	0.109		0.109
			88.50	90.00	D029526	1.50	0.053		0.053
			90.00	91.50	D029527	1.50	0.190		0.190
			91.50	93.00	D029528	1.50	0.016		0.016
			93.00	94.50	D029530	1.50	0.011		0.011
			94.50	96.00	D029531	1.50	0.121		0.121
			96.00	97.10	CIS <b>Cisaillement 50°</b>	96.00	97.50	D029532	1.50
			97.50	99.00	D029533	1.50	0.057	0.057	
			99.00	100.50	D029534	1.50	0.067	0.067	
			100.50	102.00	D029535	1.50	0.011	0.011	
			102.00	103.50	D029537	1.50	0.122	0.122	
			103.50	105.00	D029538	1.50	0.059	0.059	
105.00	171.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP automorphe ou sub arrondi, 0.3-3 cm localement zoné chloritisé	105.00	106.50	D029540	1.50	0.009		0.009
			106.50	108.00	D029541	1.50	0.007		0.007
			108.00	109.50	D029542	1.50	0.071		0.071
			109.50	111.00	D029543	1.50	0.009		0.009
			111.00	112.50	D029544	1.50	0.032		0.032
			112.50	114.00	D029545	1.50	3.400		3.400
			114.00	115.50	D029546	1.50	0.019		0.019
			115.50	117.00	D029547	1.50	0.045		0.045
			117.00	118.50	D029548	1.50	0.248		0.248
			118.50	120.00	D029550	1.50	0.019		0.019
			120.00	121.50	D029551	1.50	0.408		0.408
			121.50	123.00	D029552	1.50	0.036		0.036
			123.00	124.50	D029553	1.50	0.019		0.019
124.50	126.00	D029554	1.50	0.022		0.022			
126.00	127.50	D029555	1.50	0.009		0.009			
127.50	129.00	D029556	1.50	0.043		0.043			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	129.00	130.50	D029557	1.50	0.100		0.100
	130.50	132.00	D029558	1.50	0.087		0.087
	132.00	133.50	D029560	1.50	0.031		0.031
	133.50	135.00	D029561	1.50	0.036		0.036
	135.00	136.50	D029562	1.50	0.048		0.048
	136.50	138.00	D029563	1.50	0.018		0.018
	138.00	139.50	D029564	1.50	0.038		0.038
	139.50	141.00	D029565	1.50	0.392		0.392
	141.00	142.50	D029566	1.50	0.019		0.019
	142.50	144.00	D029567	1.50	0.046		0.046
	144.00	145.50	D029568	1.50	0.044		0.044
	145.50	147.00	D029570	1.50	0.130		0.130
	147.00	148.50	D029571	1.50	0.258		0.258
	148.50	150.00	D029572	1.50	0.018		0.018
	150.00	151.50	D029573	1.50	0.036		0.036
	151.50	153.00	D029574	1.50	0.032		0.032
	153.00	154.50	D029575	1.50	0.188		0.188
	154.50	156.00	D029577	1.50	0.036		0.036
	156.00	157.50	D029578	1.50	0.010		0.010
	157.50	159.00	D029580	1.50	0.528		0.528
	159.00	160.50	D029581	1.50	0.026		0.026
	160.50	162.00	D029582	1.50	0.024		0.024
	162.00	163.50	D029583	1.50	0.026		0.026
	163.50	165.00	D029584	1.50	0.152		0.152
	165.00	166.50	D029585	1.50	0.048		0.048
	166.50	168.00	D029586	1.50	0.297		0.297
	168.00	169.50	D029587	1.50	0.060		0.060
	169.50	171.00	D029588	1.50	0.522		0.522
	171.00	172.50	D029590	1.50	0.515		0.515
	172.50	174.00	D029591	1.50	0.460		0.460
174.00      175.50      SY; FIN <b>Syérite; Grains fins</b> passage de ± 50 cm d'intrusif basaltique amygdalaire, SR+, HM++							

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
174.00	178.70	CB03; SI03; SR03; HM02 <b>Carbonaté 3; Silicifié 3; Sérictique 3; Hématisé 2</b>	174.00	175.50	D029592	1.50	0.064		0.064			
			175.50	177.00	D029593	1.50	0.331		0.331			
			177.00	178.70	D029594	1.70	4.840		4.840			
			178.70	180.00	D029595	1.30	0.044		0.044			
			180.00	181.50	D029596	1.50	0.021		0.021			
			181.50	183.00	D029597	1.50	0.072		0.072			
			183.00	184.50	D029598	1.50	0.270		0.270			
			184.50	186.00	D029600	1.50	<0.005		0.001			
			186.00	187.50	D029601	1.50	<0.005		0.001			
			187.50	189.00	D029602	1.50	<0.005		0.001			
			189.00	190.50	D029603	1.50	<0.005		0.001			
			190.50	255.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux automorphe ou sub arrondi 0.2-2 cm zonée, altération en calcite, fortement hématisé, localement altéré en calcite	190.50	192.00	D029604	1.50	<0.005		0.001
						192.00	193.50	D029605	1.50	<0.005		0.001
						193.50	195.00	D029606	1.50	<0.005		0.001
						195.00	196.50	D029607	1.50	0.023		0.023
						196.50	198.00	D029608	1.50	0.027		0.027
						198.00	199.50	D029610	1.50	0.046		0.046
						199.50	201.00	D029611	1.50	0.095		0.095
201.00	202.50	D029612				1.50	<0.005		0.001			
202.50	204.00	D029613				1.50	0.027		0.027			
204.00	205.50	D029614				1.50	0.026		0.026			
205.50	207.00	D029615				1.50	0.019		0.019			
207.00	208.50	D029617				1.50	<0.005		0.001			
208.50	210.00	D029618				1.50	<0.005		0.001			
210.00	211.50	D029620				1.50	0.013		0.013			
211.50	213.00	D029621				1.50	0.007		0.007			
213.00	214.50	D029622	1.50	0.020		0.020						
214.50	216.00	D029623	1.50	0.031		0.031						
216.00	217.50	D029624	1.50	0.053		0.053						
217.50	219.00	D029625	1.50	0.008		0.008						
219.00	220.50	D029626	1.50	<0.005		0.001						
220.50	222.00	D029627	1.50	0.022		0.022						
222.00	223.50	D029628	1.50	<0.005		0.001						

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	223.50	225.00	D029630	1.50	<0.005		0.001
	225.00	226.50	D029631	1.50	<0.005		0.001
	226.50	228.00	D029632	1.50	0.073		0.073
	228.00	229.50	D029633	1.50	0.067		0.067
	229.50	231.00	D029634	1.50	0.006		0.006
	231.00	232.50	D029635	1.50	0.007		0.007
	232.50	234.00	D029636	1.50	<0.005		0.001
	234.00	235.50	D029637	1.50	<0.005		0.001
	235.50	237.00	D029638	1.50	<0.005		0.001
	237.00	238.50	D029640	1.50	<0.005		0.001
	238.50	240.00	D029641	1.50	0.380		0.380
	240.00	241.50	D029642	1.50	0.653		0.653
	241.50	243.00	D029643	1.50	<0.005		0.001
	243.00	244.50	D029644	1.50	<0.005		0.001
	244.50	246.00	D029645	1.50	<0.005		0.001
	246.00	247.50	D029646	1.50	<0.005		0.001
	247.50	249.00	D029647	1.50	0.092		0.092
	249.00	250.50	D029648	1.50	<0.005		0.001
	250.50	252.00	D029650	1.50	<0.005		0.001
	252.00	253.50	D029651	1.50	<0.005		0.001
	253.50	255.00	D029652	1.50	0.108		0.108
	255.00	256.50	D029653	1.50	0.005		0.005
	256.50	258.00	D029654	1.50	<0.005		0.001
	258.00	259.50	D029655	1.50	<0.005		0.001
	259.50	261.00	D029657	1.50	<0.005		0.001
	261.00	262.50	D029658	1.50	0.008		0.008
	262.50	264.00	D029660	1.50	0.013		0.013
	264.00	265.50	D029661	1.50	<0.005		0.001
	265.50	267.00	D029662	1.50	<0.005		0.001
	267.00	268.50	D029663	1.50	<0.005		0.001
	268.50	270.00	D029664	1.50	0.005		0.005
	270.00	271.50	D029665	1.50	<0.005		0.001
	271.50	273.00	D029666	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
274.80	275.10	FRC <b>Fracturé 60°</b> fragments localement millonitisés chloritisés	273.00	274.50	D029667	1.50	0.016		0.016
			274.50	276.00	D029668	1.50	0.054		0.054
			276.00	277.50	D029670	1.50	0.005		0.005
276.20	276.30	FRC <b>Fracturé 50°</b>	277.50	279.00	D029671	1.50	0.021		0.021
277.80	278.20	FRC <b>Fracturé</b> fragments mm-cm chloritisé	279.00	280.50	D029672	1.50	1.000		1.000
279.40	279.70	FRC <b>Fracturé</b>	280.50	282.00	D029673	1.50	0.216		0.216
			282.00	283.50	D029674	1.50	0.073		0.073
			283.50	285.00	D029675	1.50	0.027		0.027
			285.00	286.50	D029676	1.50	0.025		0.025
			286.50	288.00	D029677	1.50	0.011		0.011
			288.00	289.50	D029678	1.50	0.065		0.065
289.50	296.00	CB04; SR04; HM01; CH03 <b>Carbonaté 4; Séricitique 4; Hématité 1; Chloriteux 3</b>	289.50	291.00	D029680	1.50	0.016		0.016
			291.00	292.50	D029681	1.50	0.039		0.039
			292.50	294.00	D029682	1.50	0.053		0.053
			294.00	295.00	D029683	1.00	0.179		0.179
			295.00	296.00	D029684	1.00	0.054		0.054
			296.00	297.50	D029685	1.50	<0.005		0.001
297.50	312.00	SY; POR <b>Syénite; Porphyrique</b> phénocristaux de FP sub arrondi ou automorphe 0.2-0.7 cm	297.50	299.00	D029686	1.50	0.007		0.007
			299.00	300.50	D029687	1.50	<0.005		0.001
			300.50	302.00	D029688	1.50	0.047		0.047
			302.00	303.50	D029690	1.50	<0.005		0.001
			303.50	305.00	D029691	1.50	<0.005		0.001
			305.00	306.50	D029692	1.50	0.055		0.055
			306.50	308.00	D029693	1.50	<0.005		0.001
			308.00	309.50	D029694	1.50	<0.005		0.001
			309.50	311.00	D029695	1.50	<0.005		0.001
			311.00	312.50	D029697	1.50	<0.005		0.001
312.50	314.00	D029698	1.50	0.347		0.347			
314.00	315.50	D029700	1.50	0.231		0.231			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			315.50	317.00	D029701	1.50	<0.005		0.001
			317.00	318.50	D029702	1.50	<0.005		0.001
			318.50	320.00	D029703	1.50	0.089		0.089
			320.00	321.50	D029704	1.50	<0.005		0.001
			321.50	323.00	D029705	1.50	0.008		0.008
			323.00	324.50	D029706	1.50	0.008		0.008
			324.50	326.00	D029707	1.50	0.010		0.010
			326.00	327.50	D029708	1.50	<0.005		0.001
			327.50	329.00	D029710	1.50	<0.005		0.001
			329.00	330.50	D029711	1.50	0.014		0.014
			330.50	332.00	D029712	1.50	<0.005		0.001
			332.00	333.50	D029713	1.50	0.005		0.005
			333.50	335.00	D029714	1.50	<0.005		0.001
			335.00	336.50	D029715	1.50	0.373		0.373
			336.50	338.00	D029716	1.50	0.078		0.078
338.00	344.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> phénocristaux de FP sub automorphe hématisé	338.00	339.50	D029717	1.50	<0.005		0.001
			339.50	341.00	D029718	1.50	<0.005		0.001
			341.00	342.50	D029720	1.50	<0.005		0.001
			342.50	344.00	D029721	1.50	<0.005		0.001
			344.00	345.50	D029722	1.50	<0.005		0.001
			345.50	347.00	D029723	1.50	<0.005		0.001
			347.00	348.50	D029724	1.50	<0.005		0.001
			348.50	350.00	D029725	1.50	0.009		0.009
350.00	387.50	SY; POR; MOY <b>Syénite; Porphyrique; Grains moyens</b> phénocristaux de FP sub automorphe localement hématisé	350.00	351.50	D029726	1.50	<0.005		0.001
			351.50	353.00	D029727	1.50	0.012		0.012
			353.00	354.50	D029728	1.50	0.010		0.010
			354.50	356.00	D029730	1.50	<0.005		0.001
			356.00	357.50	D029731	1.50	<0.005		0.001
			357.50	359.00	D029732	1.50	0.013		0.013
			359.00	360.50	D029733	1.50	0.011		0.011
			360.50	362.00	D029734	1.50	0.006		0.006
			362.00	363.50	D029735	1.50	0.028		0.028
			363.50	365.00	D029737	1.50	0.425		0.425



Corporation Minière Osisko Div. Exploration

Description	Analyse							
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)	
	365.00	366.50	D029738	1.50	0.438		0.438	
	366.50	368.00	D029740	1.50	0.165		0.165	
	368.00	369.50	D029741	1.50	0.010		0.010	
	369.50	371.00	D029742	1.50	0.009		0.009	
	371.00	372.50	D029743	1.50	<0.005		0.001	
	372.50	374.00	D029744	1.50	0.007		0.007	
	374.00	375.50	D029745	1.50	<0.005		0.001	
	375.50	377.00	D029746	1.50	<0.005		0.001	
	377.00	378.50	D029747	1.50	0.029		0.029	
	378.50	380.00	D029748	1.50	<0.005		0.001	
	380.00	381.50	D029750	1.50	0.005		0.005	
	381.50	383.00	D029751	1.50	0.020		0.020	
	383.00	384.50	D029752	1.50	<0.005		0.001	
	384.50	386.00	D029753	1.50	<0.005		0.001	
	386.00	387.50	D029754	1.50	0.018		0.018	
	387.50	389.00	D029755	1.50	0.482		0.482	
	389.00	390.70	D029756	1.70	0.046		0.046	
	390.70	392.00	D029757	1.30	0.006		0.006	
	392.00	393.50	D029758	1.50	0.319		0.319	
	393.50	395.00	D029760	1.50	0.024		0.024	
	395.00	396.50	D029761	1.50	0.027		0.027	
	396.50	398.00	D029762	1.50	0.029		0.029	
	398.00	399.50	D029763	1.50	0.117		0.117	
	399.50	401.00	D029764	1.50	0.064		0.064	
	401.00	402.50	D029765	1.50	0.144		0.144	
	402.50	404.00	D029766	1.50	0.064		0.064	
	404.00	405.50	D029767	1.50	0.108		0.108	
	405.50	407.00	D029768	1.50	0.073		0.073	
	407.00	408.50	D029770	1.50	0.162		0.162	
	408.50	409.50	D029771	1.00	<0.005		0.001	
409.50	412.00	CIS	409.50	410.50	D029772	1.00	5.240	5.240
		<b>Cisaillement 60°</b>	410.50	412.00	D029773	1.50	1.285	1.285
			412.00	413.50	D029774	1.50	0.045	0.045

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
421.00	424.00	CIS Cisaillement 50°	413.50	415.00	D029775	1.50	0.384		0.384
			415.00	416.50	D029777	1.50	0.098		0.098
			416.50	418.00	D029778	1.50	0.247		0.247
			418.00	419.50	D029780	1.50	0.285		0.285
			419.50	421.00	D029781	1.50	0.024		0.024
			421.00	422.50	D029782	1.50	0.119		0.119
			422.50	424.00	D029783	1.50	0.347		0.347
			424.00	425.50	D029784	1.50	0.178		0.178
			425.50	427.00	D029785	1.50	0.876		0.876
			427.00	428.50	D029786	1.50	0.173		0.173
			428.50	429.70	D029787	1.20	0.273		0.273
			429.70	431.00	D029788	1.30	0.048		0.048
			431.00	432.50	D029790	1.50	<0.005		0.001
			432.50	434.00	D029791	1.50	<0.005		0.001
			434.00	435.50	D029792	1.50	0.016		0.016
			435.50	437.00	D029793	1.50	0.028		0.028
			437.00	438.50	D029794	1.50	0.908		0.908
			438.50	440.00	D029795	1.50	0.048		0.048
			440.00	441.50	D029796	1.50	0.435		0.435
			441.50	443.00	D029797	1.50	0.036		0.036
443.00	444.50	D029798	1.50	0.011		0.011			
444.50	446.00	D029800	1.50	0.008		0.008			
446.00	447.50	D029801	1.50	0.083		0.083			
447.50	449.00	D029802	1.50	0.037		0.037			
449.00	450.50	D029803	1.50	0.006		0.006			
450.50	452.00	D029804	1.50	0.006		0.006			
452.00	453.50	D029805	1.50	<0.005		0.001			
453.50	457.00	CIS Cisaillement 60°	453.50	455.00	D029806	1.50	0.080		0.080
			455.00	456.00	D029807	1.00	0.044		0.044
			456.00	457.00	D029808	1.00	0.329		0.329
			457.00	458.50	D029810	1.50	0.005		0.005
			458.50	460.00	D029811	1.50	0.024		0.024
			460.00	461.50	D029812	1.50	0.009		0.009

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	461.50	463.00	D029813	1.50	0.016		0.016
	463.00	464.50	D029814	1.50	0.018		0.018
	464.50	466.00	D029815	1.50	0.016		0.016
	466.00	467.50	D029817	1.50	0.124		0.124
	467.50	469.00	D029818	1.50	0.272		0.272
	469.00	470.50	D029820	1.50	0.008		0.008
	470.50	472.00	D029821	1.50	0.045		0.045
	472.00	473.50	D029822	1.50	0.131		0.131
	473.50	474.90	D029823	1.40	0.015		0.015
	474.90	475.90	D029824	1.00	<0.005		0.001
482.00	Fin du sondage Nombre d'échantillons : 320 Nombre d'échantillons QAQC : 45 Longueur totale échantillonnée : 473.20						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
14.50	16.00	D029469	D029468	1.50	0.104	0.104
26.70	26.70	D029479	J	0.00	0.684	0.684
39.00	40.50	D029489	D029488	1.50	<0.005	0.001
48.00	48.00	D029496	M1	0.00	<0.005	0.001
51.00	51.00	D029499	K	0.00	1.030	1.030
64.50	66.00	D029509	D029508	1.50	<0.005	0.001
78.00	78.00	D029519	L	0.00	2.000	2.000
91.50	93.00	D029529	D029528	1.50	0.016	0.016
100.50	100.50	D029536	M1	0.00	<0.005	0.001
103.50	103.50	D029539	M	0.00	3.120	3.120
117.00	118.50	D029549	D029548	1.50	0.278	0.278
130.50	130.50	D029559	J	0.00	0.754	0.754
144.00	145.50	D029569	D029568	1.50	0.038	0.038
153.00	153.00	D029576	M1	0.00	<0.005	0.001
156.00	156.00	D029579	K	0.00	1.020	1.020
169.50	171.00	D029589	D029588	1.50	0.435	0.435
183.00	183.00	D029599	L	0.00	2.330	2.330
196.50	198.00	D029609	D029608	1.50	0.029	0.029
205.50	205.50	D029616	M1	0.00	<0.005	0.001
208.50	208.50	D029619	M	0.00	3.250	3.250
222.00	223.50	D029629	D029628	1.50	<0.005	0.001
235.50	235.50	D029639	J	0.00	0.746	0.746
249.00	250.50	D029649	D029648	1.50	<0.005	0.001
258.00	258.00	D029656	M1	0.00	<0.005	0.001
261.00	261.00	D029659	K	0.00	1.085	1.085
274.50	276.00	D029669	D029668	1.50	0.022	0.022
288.00	288.00	D029679	L	0.00	2.050	2.050
300.50	302.00	D029689	D029688	1.50	0.045	0.045
309.50	309.50	D029696	M1	0.00	<0.005	0.001
312.50	312.50	D029699	M	0.00	3.140	3.140
326.00	327.50	D029709	D029708	1.50	<0.005	0.001
339.50	339.50	D029719	J	0.00	0.863	0.863
353.00	354.50	D029729	D029728	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
362.00	362.00	D029736	M1	0.00	<0.005	0.001
365.00	365.00	D029739	K	0.00	1.385	1.385
378.50	380.00	D029749	D029748	1.50	0.007	0.007
392.00	392.00	D029759	L	0.00	2.240	2.240
405.50	407.00	D029769	D029768	1.50	0.073	0.073
413.50	413.50	D029776	M1	0.00	<0.005	0.001
416.50	416.50	D029779	M	0.00	3.090	3.090
429.70	431.00	D029789	D029788	1.30	0.048	0.048
443.00	443.00	D029799	J	0.00	0.800	0.800
456.00	457.00	D029809	D029808	1.00	0.309	0.309
464.50	464.50	D029816	M1	0.00	<0.005	0.001
467.50	467.50	D029819	K	0.00	0.976	0.976

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-236**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              Guy gbaguidi

Lot :

Du :                      2010-05-22

Date de description :

Au :                      2010-05-29

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      350.00 m

Est	629 900.2
Nord	5 374 301.0
Élévation	279.7

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	11.00	0.00°	0.00°	Oui
Reflex	14.00	333.80°	-60.40°	Oui
Reflex	17.00	319.40°	-59.10°	Oui
Reflex	20.00	286.50°	-58.50°	Oui
Reflex	23.00	2.70°	-57.90°	Oui
Reflex	26.00	330.50°	-58.00°	Oui
Reflex	29.00	353.30°	-58.40°	Oui
Reflex	32.00	353.80°	-59.00°	Oui
Reflex	35.00	333.50°	-59.80°	Oui
Reflex	38.00	335.90°	-59.70°	Oui
Reflex	41.00	10.80°	-58.90°	Oui
Reflex	44.00	353.20°	-58.30°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	47.00	343.50°	-58.00°	Oui
Reflex	50.00	334.70°	-58.00°	Oui
Reflex	53.00	356.60°	-58.30°	Oui
Reflex	56.00	356.90°	-58.60°	Non
Reflex	59.00	356.70°	-58.20°	Non
Reflex	62.00	356.60°	-58.30°	Non
Reflex	65.00	356.50°	-58.30°	Non
Reflex	68.00	356.40°	-58.20°	Non
Reflex	71.00	356.30°	-58.20°	Non
Reflex	74.00	356.30°	-58.40°	Non
Reflex	77.00	356.10°	-58.40°	Non
Reflex	80.00	355.90°	-58.50°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	83.00	355.60°	-58.50°	Non
Reflex	86.00	355.60°	-58.50°	Non
Reflex	89.00	355.50°	-58.50°	Non
Reflex	92.00	355.60°	-58.60°	Non
Reflex	95.00	355.50°	-58.60°	Non
Reflex	98.00	355.60°	-58.30°	Non
Reflex	101.00	355.70°	-58.20°	Non
Reflex	104.00	355.80°	-58.30°	Non
Reflex	107.00	355.80°	-58.30°	Non
Reflex	110.00	355.60°	-58.40°	Non
Reflex	113.00	355.40°	-58.40°	Non
Reflex	116.00	356.10°	-58.30°	Non
Reflex	119.00	356.30°	-58.30°	Non
Reflex	122.00	354.20°	-58.30°	Non
Reflex	125.00	356.20°	-58.20°	Non
Reflex	128.00	356.20°	-58.10°	Non
Reflex	131.00	356.30°	-58.10°	Non
Reflex	134.00	356.20°	-58.20°	Non
Reflex	137.00	356.20°	-58.00°	Non
Reflex	140.00	356.30°	-58.00°	Non
Reflex	143.00	356.30°	-57.90°	Non
Reflex	146.00	356.20°	-57.80°	Non
Reflex	149.00	356.40°	-57.70°	Non
Reflex	152.00	356.30°	-57.70°	Non
Reflex	155.00	356.20°	-57.70°	Non
Reflex	158.00	356.30°	-57.70°	Non
Reflex	161.00	356.30°	-57.70°	Non
Reflex	164.00	356.30°	-57.60°	Non
Reflex	167.00	355.60°	-57.60°	Non
Reflex	170.00	356.30°	-57.50°	Non
Reflex	173.00	356.30°	-57.50°	Non
Reflex	176.00	356.50°	-57.40°	Non
Reflex	179.00	356.80°	-57.30°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	182.00	356.70°	-57.20°	Non
Reflex	185.00	355.00°	-57.20°	Non
Reflex	188.00	356.80°	-57.20°	Non
Reflex	191.00	355.90°	-57.20°	Non
Reflex	194.00	356.30°	-57.10°	Non
Reflex	197.00	356.90°	-57.10°	Non
Reflex	200.00	357.10°	-57.10°	Non
Reflex	203.00	357.10°	-57.10°	Non
Reflex	206.00	358.50°	-57.00°	Non
Reflex	209.00	357.00°	-57.00°	Non
Reflex	212.00	357.20°	-57.00°	Non
Reflex	215.00	355.80°	-57.00°	Non
Reflex	218.00	357.60°	-57.00°	Non
Reflex	221.00	357.70°	-57.00°	Non
Reflex	224.00	357.70°	-57.00°	Non
Reflex	227.00	357.50°	-56.90°	Non
Reflex	230.00	357.90°	-56.90°	Non
Reflex	233.00	357.90°	-56.90°	Non
Reflex	236.00	357.90°	-56.80°	Non
Reflex	239.00	357.90°	-56.80°	Non
Reflex	242.00	357.80°	-56.80°	Non
Reflex	245.00	358.70°	-56.80°	Non
Reflex	248.00	358.80°	-56.80°	Non
Reflex	251.00	356.90°	-56.80°	Non
Reflex	254.00	358.10°	-56.80°	Non
Reflex	257.00	358.40°	-56.90°	Non
Reflex	260.00	358.30°	-56.80°	Non
Reflex	263.00	358.30°	-56.80°	Non
Reflex	266.00	358.10°	-56.70°	Non
Reflex	269.00	358.10°	-56.70°	Non
Reflex	272.00	358.50°	-56.90°	Non
Reflex	275.00	359.00°	-56.90°	Non
Reflex	278.00	359.20°	-56.90°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	281.00	358.80°	-56.90°	Non					
Reflex	284.00	359.00°	-56.90°	Non					
Reflex	287.00	359.00°	-56.90°	Non					
Reflex	290.00	359.10°	-56.90°	Non					
Reflex	293.00	358.90°	-56.90°	Non					
Reflex	296.00	359.20°	-56.90°	Non					
Reflex	299.00	359.30°	-56.90°	Non					
Reflex	302.00	359.20°	-56.80°	Non					
Reflex	305.00	359.20°	-56.80°	Non					
Reflex	308.00	359.20°	-56.80°	Non					
Reflex	311.00	359.50°	-56.90°	Non					
Reflex	314.00	359.40°	-56.90°	Non					
Reflex	317.00	359.60°	-57.00°	Non					
Reflex	320.00	359.70°	-57.00°	Non					
Reflex	323.00	359.60°	-56.90°	Non					
Reflex	326.00	359.50°	-56.80°	Non					
Reflex	329.00	359.60°	-56.90°	Non					
Reflex	332.00	359.60°	-56.90°	Non					
Reflex	335.00	359.70°	-56.90°	Non					
Reflex	338.00	359.60°	-56.90°	Non					
Reflex	341.00	359.20°	-56.70°	Non					
Reflex	344.00	0.40°	-57.10°	Non					
Reflex	347.00	0.70°	-57.00°	Non					
Reflex	350.00	1.00°	-57.00°	Non					



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	48.30	MT						
		<b>Mort-terrain</b>						
48.30	209.00	ST	48.30	49.70	D023988	1.40	0.005	0.005
		<b>Siltstone 30°</b>	49.70	51.00	D023989	1.30	0.006	0.006
		Massive, séricitisé, localement graphiteux, fortement carbonaté.	51.00	52.50	D023990	1.50	<0.005	0.001
			52.50	54.00	D023991	1.50	0.027	0.027
			54.00	55.00	D023992	1.00	<0.005	0.001
			55.00	56.50	D023993	1.50	<0.005	0.001
			56.50	58.00	D023994	1.50	0.009	0.009
			58.00	59.50	D023996	1.50	0.005	0.005
			59.50	61.00	D023997	1.50	0.005	0.005
			61.00	62.50	D023998	1.50	0.007	0.007
			62.50	64.00	D023999	1.50	<0.005	0.001
			64.00	65.00	D024000	1.00	0.005	0.005
			65.00	66.50	D024001	1.50	0.012	0.012
			66.50	67.50	D024002	1.00	0.013	0.013
			67.50	68.60	D024003	1.10	0.020	0.020
			68.60	70.00	D024004	1.40	0.014	0.014
			70.00	71.00	D024006	1.00	0.005	0.005
			71.00	72.50	D024007	1.50	<0.005	0.001
			72.50	74.00	D024008	1.50	0.010	0.010
			74.00	75.20	D024009	1.20	0.006	0.006
			75.20	76.90	D024010	1.70	<0.005	0.001
			76.90	78.50	D024011	1.60	<0.005	0.001
			78.50	80.00	D024012	1.50	<0.005	0.001
			80.00	81.40	D024013	1.40	<0.005	0.001
			81.40	83.00	D024014	1.60	0.007	0.007
			83.00	84.50	D024016	1.50	<0.005	0.001
			84.50	86.00	D024017	1.50	<0.005	0.001
			86.00	87.00	D024018	1.00	<0.005	0.001
			87.00	88.00	D024019	1.00	<0.005	0.001
			88.00	89.00	D024020	1.00	<0.005	0.001
			89.00	90.50	D024021	1.50	<0.005	0.001
			90.50	92.00	D024022	1.50	0.005	0.005

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	92.00	93.50	D024023	1.50	<0.005		0.001
	93.50	95.00	D024024	1.50	<0.005		0.001
	95.00	96.50	D024026	1.50	<0.005		0.001
	96.50	98.00	D024027	1.50	<0.005		0.001
	98.00	99.00	D024028	1.00	<0.005		0.001
	99.00	100.50	D024029	1.50	<0.005		0.001
	100.50	102.00	D024030	1.50	<0.005		0.001
	102.00	103.50	D024031	1.50	<0.005		0.001
	103.50	105.00	D024032	1.50	<0.005		0.001
	105.00	106.50	D024033	1.50	<0.005		0.001
	106.50	108.00	D024034	1.50	0.005		0.005
	108.00	109.50	D024036	1.50	<0.005		0.001
	109.50	111.00	D024037	1.50	<0.005		0.001
	111.00	112.50	D024038	1.50	<0.005		0.001
	112.50	114.00	D024039	1.50	<0.005		0.001
	114.00	115.50	D024041	1.50	<0.005		0.001
	115.50	117.00	D024042	1.50	<0.005		0.001
	117.00	118.50	D024043	1.50	0.006		0.006
	118.50	120.00	D024044	1.50	<0.005		0.001
	120.00	121.50	D024046	1.50	<0.005		0.001
	121.50	123.00	D024047	1.50	<0.005		0.001
	123.00	124.50	D024048	1.50	<0.005		0.001
	124.50	126.00	D024049	1.50	<0.005		0.001
	126.00	127.50	D024050	1.50	0.005		0.005
	127.50	129.00	D024051	1.50	<0.005		0.001
	129.00	130.50	D024052	1.50	<0.005		0.001
	130.50	132.00	D024053	1.50	<0.005		0.001
	132.00	133.50	D024054	1.50	0.005		0.005
	133.50	135.00	D024056	1.50	<0.005		0.001
	135.00	136.50	D024057	1.50	<0.005		0.001
	136.50	138.00	D024058	1.50	<0.005		0.001
	138.00	139.50	D024059	1.50	<0.005		0.001
	139.50	141.00	D024060	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	141.00	142.50	D024061	1.50	<0.005		0.001
	142.50	144.00	D024062	1.50	<0.005		0.001
	144.00	145.50	D024063	1.50	<0.005		0.001
	145.50	147.00	D024064	1.50	0.005		0.005
	147.00	148.50	D024066	1.50	<0.005		0.001
	148.50	150.00	D024067	1.50	<0.005		0.001
	150.00	151.50	D024068	1.50	0.005		0.005
	151.50	153.00	D024069	1.50	<0.005		0.001
	153.00	154.50	D024070	1.50	0.006		0.006
	154.50	156.00	D024071	1.50	<0.005		0.001
	156.00	157.50	D024072	1.50	<0.005		0.001
	157.50	159.00	D024073	1.50	<0.005		0.001
	159.00	160.50	D024074	1.50	<0.005		0.001
	160.50	162.00	D024076	1.50	<0.005		0.001
	162.00	163.50	D024077	1.50	<0.005		0.001
	163.50	165.00	D024078	1.50	0.010		0.010
	165.00	166.50	D024079	1.50	0.007		0.007
	166.50	168.00	D024081	1.50	<0.005		0.001
	168.00	169.50	D024082	1.50	<0.005		0.001
	169.50	171.00	D024083	1.50	<0.005		0.001
	171.00	172.50	D024084	1.50	<0.005		0.001
	172.50	174.00	D024086	1.50	<0.005		0.001
	174.00	175.50	D024087	1.50	<0.005		0.001
	175.50	177.00	D024088	1.50	<0.005		0.001
	177.00	178.50	D024089	1.50	<0.005		0.001
	178.50	180.00	D024090	1.50	<0.005		0.001
	180.00	181.50	D024091	1.50	<0.005		0.001
	181.50	183.00	D024092	1.50	<0.005		0.001
	183.00	184.50	D024093	1.50	<0.005		0.001
	184.50	186.00	D024094	1.50	<0.005		0.001
	186.00	187.50	D024096	1.50	<0.005		0.001
	187.50	189.00	D024097	1.50	<0.005		0.001
	189.00	190.50	D024098	1.50	0.006		0.006

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			190.50	192.00	D024099	1.50	<0.005		0.001
			192.00	193.50	D024100	1.50	<0.005		0.001
			193.50	195.00	D024101	1.50	<0.005		0.001
			195.00	196.50	D024102	1.50	<0.005		0.001
			196.50	198.00	D024103	1.50	<0.005		0.001
			198.00	199.50	D024104	1.50	<0.005		0.001
			199.50	201.00	D024106	1.50	0.005		0.005
			201.00	202.00	D024107	1.00	0.005		0.005
			202.00	203.00	D024108	1.00	<0.005		0.001
			203.00	204.50	D024109	1.50	0.005		0.005
			204.50	206.00	D024110	1.50	0.005		0.005
			206.00	207.50	D024111	1.50	0.008		0.008
			207.50	209.00	D024112	1.50	0.007		0.007
209.00	212.60	SY; POR <b>Syénite 30°; Porphyrique</b> Fortement carbonatée, séricitisée, phénocristaux fins à grossiers et orientés à 20-30°.	209.00	210.50	D024113	1.50	<0.005		0.001
			210.50	211.50	D024114	1.00	<0.005		0.001
			211.50	212.60	D024116	1.10	<0.005		0.001
212.60	219.00	ST <b>Siltstone</b> Massive, séricitisé, fortement carbonaté.	212.60	214.00	D024117	1.40	<0.005		0.001
			214.00	215.50	D024118	1.50	<0.005		0.001
			215.50	217.00	D024119	1.50	<0.005		0.001
			217.00	218.00	D024121	1.00	0.005		0.005
			218.00	219.00	D024122	1.00	<0.005		0.001
219.00	224.50	BA <b>Basalte</b> Basalte massive fortement carbonaté.	219.00	220.00	D024123	1.00	<0.005		0.001
			220.00	221.50	D024124	1.50	<0.005		0.001
			221.50	223.00	D024126	1.50	<0.005		0.001
			223.00	224.50	D024127	1.50	<0.005		0.001
224.50	237.50	GA <b>Gabbro 25°</b> Gabbro à leucocène.	224.50	226.00	D024128	1.50	<0.005		0.001
			226.00	227.50	D024129	1.50	<0.005		0.001
			227.50	229.00	D024130	1.50	0.005		0.005
			229.00	230.50	D024131	1.50	<0.005		0.001
			230.50	232.00	D024132	1.50	<0.005		0.001
			232.00	233.50	D024133	1.50	<0.005		0.001
			233.50	235.00	D024134	1.50	<0.005		0.001
			235.00	236.50	D024136	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
237.50	249.40	BA <b>Basalte 20°</b> Séricitisé, massive à gf.	236.50	237.70	D024137	1.20	<0.005		0.001
			237.70	239.40	D024138	1.70	<0.005		0.001
			239.40	241.00	D024139	1.60	<0.005		0.001
			241.00	242.50	D024140	1.50	<0.005		0.001
			242.50	244.00	D024141	1.50	<0.005		0.001
			244.00	245.50	D024142	1.50	<0.005		0.001
			245.50	247.00	D024143	1.50	<0.005		0.001
			247.00	248.00	D024144	1.00	<0.005		0.001
			248.00	249.40	D024146	1.40	<0.005		0.001
249.40	256.00	ST <b>Siltstone 25°</b> Massive à gf, carbonaté, séricitisé.	249.40	251.00	D024147	1.60	<0.005		0.001
			251.00	252.50	D024148	1.50	<0.005		0.001
			252.50	254.00	D024149	1.50	<0.005		0.001
			254.00	255.00	D024150	1.00	<0.005		0.001
			255.00	256.00	D024151	1.00	<0.005		0.001
256.00	270.50	GA <b>Gabbro 30°</b> Gabbro à leucocène carbonaté.	256.00	257.50	D024152	1.50	<0.005		0.001
			257.50	259.00	D024153	1.50	<0.005		0.001
			259.00	260.50	D024154	1.50	<0.005		0.001
			260.50	262.00	D024156	1.50	<0.005		0.001
			262.00	263.50	D024157	1.50	<0.005		0.001
			263.50	265.00	D024158	1.50	<0.005		0.001
			265.00	266.50	D024159	1.50	<0.005		0.001
			266.50	268.00	D024161	1.50	<0.005		0.001
			268.00	269.50	D024162	1.50	<0.005		0.001
270.50	350.00	BA <b>Basalte</b> Carbonaté et amygdalaire.	269.50	270.50	D024163	1.00	<0.005		0.001
			270.50	272.00	D024164	1.50	<0.005		0.001
			272.00	273.50	D024166	1.50	<0.005		0.001
			273.50	275.00	D024167	1.50	<0.005		0.001
			275.00	276.50	D024168	1.50	<0.005		0.001
			276.50	278.00	D024169	1.50	<0.005		0.001
			278.00	279.50	D024170	1.50	<0.005		0.001
			279.50	281.00	D024171	1.50	<0.005		0.001
			281.00	282.50	D024172	1.50	<0.005		0.001
282.50	284.00	D024173	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	284.00	285.50	D024174	1.50	<0.005		0.001
	285.50	287.00	D024176	1.50	<0.005		0.001
	287.00	288.50	D024177	1.50	<0.005		0.001
	288.50	290.00	D024178	1.50	<0.005		0.001
	290.00	291.60	D024179	1.60	<0.005		0.001
	291.60	293.00	D024180	1.40	<0.005		0.001
	293.00	294.50	D024181	1.50	<0.005		0.001
	294.50	296.00	D024182	1.50	<0.005		0.001
	296.00	297.50	D024183	1.50	<0.005		0.001
	297.50	299.00	D024184	1.50	<0.005		0.001
	299.00	300.50	D024186	1.50	<0.005		0.001
	300.50	302.00	D024187	1.50	<0.005		0.001
	302.00	303.50	D024188	1.50	<0.005		0.001
	303.50	305.00	D024189	1.50	<0.005		0.001
	305.00	306.50	D024190	1.50	<0.005		0.001
	306.50	308.00	D024191	1.50	<0.005		0.001
	308.00	309.50	D024192	1.50	<0.005		0.001
	309.50	311.00	D024193	1.50	<0.005		0.001
	311.00	312.50	D024194	1.50	<0.005		0.001
	312.50	314.00	D024196	1.50	0.005		0.005
	314.00	315.50	D024197	1.50	<0.005		0.001
	315.50	317.00	D024198	1.50	<0.005		0.001
	317.00	318.50	D024199	1.50	<0.005		0.001
	318.50	320.00	D024201	1.50	<0.005		0.001
	320.00	321.50	D024202	1.50	<0.005		0.001
	321.50	323.00	D024203	1.50	<0.005		0.001
	323.00	324.50	D024204	1.50	<0.005		0.001
	324.50	326.00	D024206	1.50	<0.005		0.001
	326.00	327.50	D024207	1.50	<0.005		0.001
	327.50	329.00	D024208	1.50	<0.005		0.001
	329.00	330.50	D024209	1.50	<0.005		0.001
	330.50	332.00	D024210	1.50	<0.005		0.001
	332.00	333.50	D024211	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	333.50	335.00	D024212	1.50	<0.005		0.001
	335.00	336.50	D024213	1.50	<0.005		0.001
	336.50	338.00	D024214	1.50	<0.005		0.001
	338.00	339.50	D024216	1.50	<0.005		0.001
	339.50	341.00	D024217	1.50	<0.005		0.001
	341.00	342.50	D024218	1.50	<0.005		0.001
	342.50	344.00	D024219	1.50	<0.005		0.001
	344.00	345.50	D024220	1.50	<0.005		0.001
	345.50	347.00	D024221	1.50	<0.005		0.001
	347.00	348.50	D024222	1.50	0.006		0.006
	348.50	350.00	D024223	1.50	<0.005		0.001
350.00	Fin du sondage Nombre d'échantillons : 208 Nombre d'échantillons QAQC : 28 Longueur totale échantillonnée : 301.70						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
56.50	56.50	D023995	K	0.00	1.040	1.040
68.60	70.00	D024005	D024004	1.40	0.013	0.013
81.40	81.40	D024015	J	0.00	0.722	0.722
93.50	95.00	D024025	D024024	1.50	<0.005	0.001
106.50	106.50	D024035	K	0.00	1.070	1.070
112.50	112.50	D024040	M1	0.00	<0.005	0.001
118.50	120.00	D024045	D024044	1.50	<0.005	0.001
132.00	132.00	D024055	L	0.00	2.220	2.220
145.50	147.00	D024065	D024064	1.50	<0.005	0.001
159.00	159.00	D024075	M	0.00	3.170	3.170
165.00	165.00	D024080	M1	0.00	<0.005	0.001
171.00	172.50	D024085	D024084	1.50	<0.005	0.001
184.50	184.50	D024095	J	0.00	0.781	0.781
198.00	199.50	D024105	D024104	1.50	<0.005	0.001
210.50	210.50	D024115	K	0.00	0.947	0.947
215.50	215.50	D024120	M1	0.00	<0.005	0.001
220.00	221.50	D024125	D024124	1.50	0.005	0.005
233.50	233.50	D024135	J	0.00	0.756	0.756
247.00	248.00	D024145	D024144	1.00	<0.005	0.001
259.00	259.00	D024155	K	0.00	1.045	1.045
265.00	265.00	D024160	M1	0.00	<0.005	0.001
270.50	272.00	D024165	B024164	1.50	<0.005	0.001
284.00	284.00	D024175	L	0.00	2.100	2.100
297.50	299.00	D024185	B024184	1.50	<0.005	0.001
311.00	311.00	D024195	M	0.00	3.190	3.190
317.00	317.00	D024200	M1	0.00	<0.005	0.001
323.00	324.50	D024205	B024204	1.50	<0.005	0.001
336.50	336.50	D024215	J	0.00	0.714	0.714



## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-237**

Titre minier :

Section :                      629900

Canton :

Niveau :

Foré par :                      Bradley

Rang :

Place de travail :              Malartic

Décrit par :                      Gilles.KAMTA

Lot :

Du :                              2010-05-14

Date de description :              2010-07-06

Au :                              2010-05-17

Collet

UTM

Azimut :                      180.00°

Plongée :                      -62.00°

Longueur :                      287.00 m

Est                              629 899.9

Nord                              5 374 298.6

Élévation                      279.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	340.80°	-61.50°	Oui
Reflex	8.00	326.70°	-60.80°	Oui
Reflex	11.00	3.80°	-60.70°	Oui
Reflex	14.00	340.90°	-63.00°	Oui
Reflex	17.00	357.70°	-59.80°	Oui
Reflex	20.00	334.00°	-59.80°	Oui
Reflex	23.00	333.60°	-59.80°	Oui
Reflex	26.00	340.70°	-58.90°	Oui
Reflex	29.00	323.70°	-59.60°	Oui
Reflex	32.00	337.50°	-59.70°	Oui
Reflex	35.00	1.30°	-60.10°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	337.00°	-59.30°	Oui
Reflex	41.00	339.30°	-59.60°	Oui
Reflex	44.00	338.90°	-58.50°	Oui
Reflex	47.00	349.20°	-60.00°	Oui
Reflex	50.00	182.90°	-57.50°	Oui
Reflex	53.00	180.80°	-59.20°	Non
Reflex	56.00	181.20°	-59.00°	Non
Reflex	59.00	181.60°	-58.30°	Non
Reflex	62.00	181.00°	-58.40°	Non
Reflex	65.00	181.20°	-58.40°	Non
Reflex	68.00	181.30°	-58.80°	Non
Reflex	71.00	181.40°	-58.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	178.90°	-52.90°	Oui	Reflex	173.00	179.00°	-56.80°	Non
Reflex	77.00	180.90°	-59.80°	Non	Reflex	176.00	178.30°	-56.50°	Non
Reflex	80.00	181.30°	-58.50°	Non	Reflex	179.00	178.00°	-56.50°	Non
Reflex	83.00	181.20°	-58.50°	Non	Reflex	182.00	178.10°	-56.40°	Non
Reflex	86.00	181.10°	-58.50°	Non	Reflex	185.00	178.00°	-56.20°	Non
Reflex	89.00	245.20°	-42.90°	Oui	Reflex	188.00	177.80°	-56.10°	Non
Reflex	92.00	181.40°	-58.30°	Non	Reflex	191.00	177.90°	-56.10°	Non
Reflex	95.00	181.50°	-58.20°	Non	Reflex	194.00	177.90°	-55.90°	Non
Reflex	98.00	181.20°	-58.10°	Non	Reflex	197.00	177.70°	-55.80°	Non
Reflex	101.00	181.20°	-58.00°	Non	Reflex	200.00	177.80°	-55.80°	Non
Reflex	104.00	183.10°	-58.20°	Non	Reflex	203.00	177.60°	-55.70°	Non
Reflex	107.00	181.50°	-57.80°	Non	Reflex	206.00	177.60°	-55.60°	Non
Reflex	110.00	181.10°	-57.80°	Non	Reflex	209.00	177.70°	-55.60°	Non
Reflex	113.00	181.00°	-57.70°	Non	Reflex	212.00	177.40°	-55.60°	Non
Reflex	116.00	180.90°	-57.70°	Non	Reflex	215.00	177.60°	-55.60°	Non
Reflex	119.00	187.10°	-57.30°	Oui	Reflex	218.00	177.40°	-55.60°	Non
Reflex	122.00	180.50°	-57.50°	Non	Reflex	221.00	177.30°	-55.60°	Non
Reflex	125.00	180.50°	-57.50°	Non	Reflex	224.00	177.30°	-55.50°	Non
Reflex	128.00	180.20°	-57.40°	Non	Reflex	227.00	177.30°	-55.50°	Non
Reflex	131.00	179.90°	-57.30°	Non	Reflex	230.00	177.40°	-55.50°	Non
Reflex	134.00	179.50°	-57.10°	Non	Reflex	233.00	177.10°	-55.50°	Non
Reflex	137.00	179.50°	-57.10°	Non	Reflex	236.00	177.00°	-55.40°	Non
Reflex	140.00	179.40°	-57.10°	Non	Reflex	239.00	176.70°	-55.30°	Non
Reflex	143.00	179.40°	-57.00°	Non	Reflex	242.00	176.50°	-55.30°	Non
Reflex	146.00	179.30°	-57.10°	Non	Reflex	245.00	176.60°	-55.30°	Non
Reflex	149.00	179.30°	-57.10°	Non	Reflex	248.00	176.70°	-55.30°	Non
Reflex	152.00	179.30°	-57.00°	Non	Reflex	251.00	176.30°	-55.20°	Non
Reflex	155.00	179.10°	-57.10°	Non	Reflex	254.00	176.20°	-55.20°	Non
Reflex	158.00	178.90°	-57.10°	Non	Reflex	257.00	176.30°	-55.10°	Non
Reflex	161.00	179.10°	-57.00°	Non	Reflex	260.00	176.30°	-55.00°	Non
Reflex	164.00	179.00°	-57.00°	Non	Reflex	263.00	176.30°	-54.90°	Non
Reflex	167.00	179.10°	-57.00°	Non	Reflex	266.00	176.10°	-54.70°	Non
Reflex	170.00	179.10°	-57.00°	Non	Reflex	269.00	175.50°	-54.50°	Non



Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	44.50	MT						
		<b>Mort-terrain</b>						
44.50	75.00	GR; MAS; FIN	44.50	46.00	D028184	1.50	<0.005	0.001
		<b>Grès; Roche massive; Grains fins</b>	46.00	47.50	D028185	1.50	<0.005	0.001
		grenue, localement laminations, altération en calcite, chlorite et séricite, veines et veinules de calcite, PY fine irrég diss	47.50	49.00	D028186	1.50	<0.005	0.001
			49.00	50.50	D028187	1.50	<0.005	0.001
			50.50	52.00	D028188	1.50	<0.005	0.001
			52.00	53.50	D028189	1.50	<0.005	0.001
			53.50	55.00	D028190	1.50	<0.005	0.001
			55.00	56.50	D028191	1.50	<0.005	0.001
			56.50	58.00	D028192	1.50	<0.005	0.001
			58.00	59.50	D028194	1.50	<0.005	0.001
			59.50	61.00	D028195	1.50	<0.005	0.001
			61.00	62.50	D028196	1.50	<0.005	0.001
			62.50	64.00	D028197	1.50	<0.005	0.001
			64.00	65.50	D028198	1.50	<0.005	0.001
			65.50	67.00	D028199	1.50	<0.005	0.001
			67.00	68.50	D028200	1.50	<0.005	0.001
			68.50	70.00	D028201	1.50	<0.005	0.001
			70.00	71.50	D028202	1.50	<0.005	0.001
			71.50	73.00	D028204	1.50	<0.005	0.001
			73.00	74.00	D028205	1.00	<0.005	0.001
			74.00	75.00	D028206	1.00	<0.005	0.001
75.00	129.20	GA; MAS; FIN	75.00	76.50	D028207	1.50	<0.005	0.001
		<b>Gabbro 60°; Roche massive; Grains fins</b>	76.50	78.00	D028208	1.50	<0.005	0.001
		grenue grains moyen à fin, chloritisé, localement séricitisé, altération en calcite, carbonâtes, veines et veinules de calcite	78.00	79.50	D028209	1.50	<0.005	0.001
			79.50	81.00	D028210	1.50	<0.005	0.001
			81.00	82.50	D028211	1.50	<0.005	0.001
			82.50	84.00	D028212	1.50	<0.005	0.001
			84.00	85.50	D028214	1.50	<0.005	0.001
			85.50	87.00	D028215	1.50	<0.005	0.001
			87.00	88.50	D028216	1.50	<0.005	0.001
			88.50	90.00	D028217	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			90.00	91.50	D028218	1.50	<0.005		0.001
			91.50	93.00	D028219	1.50	<0.005		0.001
			93.00	94.50	D028221	1.50	0.008		0.008
			94.50	96.00	D028222	1.50	<0.005		0.001
			96.00	97.50	D028224	1.50	0.006		0.006
			97.50	99.00	D028225	1.50	<0.005		0.001
			99.00	100.50	D028226	1.50	0.050		0.050
			100.50	102.00	D028227	1.50	<0.005		0.001
			102.00	103.50	D028228	1.50	<0.005		0.001
			103.50	105.00	D028229	1.50	0.005		0.005
			105.00	106.50	D028230	1.50	0.007		0.007
			106.50	108.00	D028231	1.50	<0.005		0.001
			108.00	109.50	D028232	1.50	<0.005		0.001
			109.50	111.00	D028234	1.50	<0.005		0.001
			111.00	112.50	D028235	1.50	<0.005		0.001
			112.50	114.00	D028236	1.50	<0.005		0.001
			114.00	115.50	D028237	1.50	<0.005		0.001
			115.50	117.00	D028238	1.50	0.009		0.009
			117.00	118.50	D028239	1.50	0.005		0.005
			118.50	120.00	D028240	1.50	<0.005		0.001
			120.00	121.50	D028241	1.50	<0.005		0.001
			121.50	123.00	D028242	1.50	0.013		0.013
			123.00	124.50	D028244	1.50	0.008		0.008
			124.50	126.00	D028245	1.50	0.007		0.007
			126.00	127.50	D028246	1.50	<0.005		0.001
			127.50	129.20	D028247	1.70	0.007		0.007
129.20	147.00	ST; MAS	129.20	130.50	D028248	1.30	0.013		0.013
		<b>Siltstone 70°; Roche massive</b>	130.50	132.00	D028249	1.50	<0.005		0.001
		grenue à grains fin, localement laminations, intercalations de graphite,	132.00	133.50	D028250	1.50	<0.005		0.001
		PY en amas fin, chlorite, biotite	133.50	135.00	D028251	1.50	<0.005		0.001
			135.00	136.10	D028252	1.10	0.014		0.014
			136.10	137.40	D028254	1.30	0.027		0.027
			137.40	139.00	D028255	1.60	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
147.00	163.40	UM; MAS <b>Ultramaïte serpentinisée 60°; Roche massive</b> massive localement cisailé, veinules et cheveux carbonaté, CL++, talc	139.00	140.50	D028256	1.50	0.007		0.007
			140.50	142.00	D028257	1.50	0.022		0.022
			142.00	143.50	D028258	1.50	0.006		0.006
			143.50	145.00	D028259	1.50	0.013		0.013
			145.00	146.00	D028261	1.00	0.020		0.020
			146.00	147.00	D028262	1.00	0.055		0.055
			147.00	148.50	D028264	1.50	0.021		0.021
			148.50	150.00	D028265	1.50	0.019		0.019
			150.00	151.50	D028266	1.50	<0.005		0.001
			151.50	153.00	D028267	1.50	<0.005		0.001
			153.00	154.50	D028268	1.50	<0.005		0.001
			154.50	156.00	D028269	1.50	<0.005		0.001
			156.00	157.50	D028270	1.50	<0.005		0.001
			157.50	159.00	D028271	1.50	<0.005		0.001
158.80	159.00	FAI <b>Faille 70°</b> boue verdâtre	159.00	160.50	D028272	1.50	0.014		0.014
			160.50	162.00	D028274	1.50	<0.005		0.001
			162.00	163.40	D028275	1.40	0.006		0.006
163.40	204.00	GR; MAS; FIN <b>Grès 30°; Roche massive; Grains fins</b> équigranulaire, passage de silstone et mudstone légèrement laminé et schisteux, altération en calcite, séricite et chlorite, PY fine irrég diss	163.40	165.00	D028276	1.60	0.020		0.020
			165.00	166.50	D028277	1.50	0.012		0.012
			166.50	168.00	D028278	1.50	0.009		0.009
			168.00	169.50	D028279	1.50	0.008		0.008
			169.50	171.00	D028280	1.50	0.006		0.006
			171.00	172.50	D028281	1.50	0.007		0.007
			172.50	174.00	D028282	1.50	0.010		0.010
			174.00	175.50	D028284	1.50	0.047		0.047
			175.50	177.00	D028285	1.50	0.023		0.023
			177.00	178.50	D028286	1.50	0.016		0.016
			178.50	180.00	D028287	1.50	0.061		0.061
			180.00	181.50	D028288	1.50	0.006		0.006
			181.50	183.00	D028289	1.50	0.010		0.010
			183.00	184.50	D028290	1.50	0.007		0.007
184.50	186.00	D028291	1.50	0.008		0.008			
186.00	187.50	D028292	1.50	0.014		0.014			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
204.00	287.00	ST; FIN <b>Siltstone 60°; Grains fins</b> grenue, litage, localement alternance de lits fin de siltstone et mudstone à séricite et chlorite, pseudo foliation 60-80° ac, schistosité, localement galets, jaspe, veines de QZ carbonaté, SR++, CL++, PY fine irrég diss	187.50	189.00	D028294	1.50	0.006		0.006
			189.00	190.50	D028295	1.50	0.017		0.017
			190.50	192.00	D028296	1.50	0.006		0.006
			192.00	193.50	D028297	1.50	0.007		0.007
			193.50	195.00	D028298	1.50	<0.005		0.001
			195.00	196.50	D028299	1.50	0.008		0.008
			196.50	198.00	D028301	1.50	0.006		0.006
			198.00	199.50	D028302	1.50	0.006		0.006
			199.50	201.00	D028304	1.50	<0.005		0.001
			201.00	202.50	D028305	1.50	<0.005		0.001
			202.50	204.00	D028306	1.50	<0.005		0.001
			204.00	205.50	D028307	1.50	0.218		0.218
			205.50	207.00	D028308	1.50	0.016		0.016
			207.00	208.50	D028309	1.50	0.007		0.007
			208.50	210.00	D028310	1.50	0.096		0.096
			210.00	211.50	D028311	1.50	0.088		0.088
			211.50	213.00	D028312	1.50	0.177		0.177
			213.00	214.50	D028314	1.50	0.039		0.039
			214.50	216.00	D028315	1.50	0.093		0.093
			216.00	217.50	D028316	1.50	0.011		0.011
			217.50	219.00	D028317	1.50	0.025		0.025
			219.00	220.50	D028318	1.50	0.116		0.116
			220.50	222.00	D028319	1.50	0.057		0.057
			222.00	223.50	D028320	1.50	0.056		0.056
			223.50	225.00	D028321	1.50	0.167		0.167
			225.00	226.50	D028322	1.50	0.013		0.013
			226.50	228.00	D028324	1.50	0.622		0.622
			228.00	229.50	D028325	1.50	0.020		0.020
			229.50	231.00	D028326	1.50	0.005		0.005
			231.00	232.50	D028327	1.50	0.050		0.050
232.50	234.00	D028328	1.50	0.010		0.010			
234.00	235.50	D028329	1.50	0.033		0.033			
235.50	237.00	D028330	1.50	0.042		0.042			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
241.50	243.00	FRC Fracturé 40° fragment cm avec boue de faille verdâtre	237.00	238.50	D028331	1.50	0.048		0.048
			238.50	240.00	D028332	1.50	0.020		0.020
			240.00	241.50	D028334	1.50	0.011		0.011
			241.50	243.00	D028335	1.50	0.076		0.076
			243.00	244.50	D028336	1.50	0.075		0.075
			244.50	246.00	D028337	1.50	0.034		0.034
			246.00	247.50	D028338	1.50	0.022		0.022
			247.50	249.00	D028339	1.50	0.006		0.006
			249.00	250.50	D028341	1.50	0.067		0.067
			250.50	252.00	D028342	1.50	0.312		0.312
			252.00	253.50	D028344	1.50	0.178		0.178
			253.50	255.00	D028345	1.50	0.010		0.010
			255.00	256.50	D028346	1.50	<0.005		0.001
			256.50	258.00	D028347	1.50	0.013		0.013
			258.00	259.50	D028348	1.50	0.009		0.009
			259.50	261.00	D028349	1.50	0.006		0.006
			261.00	262.50	D028350	1.50	0.028		0.028
			262.50	264.00	D028351	1.50	0.025		0.025
			264.00	265.50	D028352	1.50	0.011		0.011
			265.50	267.00	D028354	1.50	0.011		0.011
			267.00	268.50	D028355	1.50	<0.005		0.001
			268.50	270.00	D028356	1.50	0.031		0.031
			270.00	271.50	D028357	1.50	0.012		0.012
			271.50	273.00	D028358	1.50	0.018		0.018
			273.00	274.50	D028359	1.50	0.082		0.082
			274.50	276.00	D028360	1.50	0.010		0.010
			276.00	277.50	D028361	1.50	0.011		0.011
			277.50	279.00	D028362	1.50	0.042		0.042
			279.00	280.50	D028364	1.50	0.014		0.014
			280.50	282.00	D028365	1.50	0.031		0.031
282.00	283.50	D028366	1.50	0.033		0.033			
283.50	285.00	D028367	1.50	0.017		0.017			
285.00	286.00	D028368	1.00	0.005		0.005			



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	286.00	287.00	D028369	1.00	0.006		0.006
287.00    Fin du sondage Nombre d'échantillons : 164 Nombre d'échantillons QAQC : 22 Longueur totale échantillonnée : 242.50							

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
56.50	58.00	D028193	D028192	1.50	<0.005	0.001
70.00	70.00	D028203	J	0.00	0.717	0.717
82.50	84.00	D028213	D028212	1.50	<0.005	0.001
91.50	91.50	D028220	M1	0.00	<0.005	0.001
94.50	94.50	D028223	K	0.00	0.992	0.992
108.00	109.50	D028233	D028232	1.50	<0.005	0.001
121.50	121.50	D028243	L	0.00	2.160	2.160
135.00	136.10	D028253	D028252	1.10	0.014	0.014
143.50	143.50	D028260	M1	0.00	<0.005	0.001
146.00	146.00	D028263	K	0.00	0.997	0.997
159.00	160.50	D028273	D028272	1.50	<0.005	0.001
172.50	172.50	D028283	J	0.00	0.784	0.784
186.00	187.50	D028293	D028292	1.50	0.013	0.013
196.50	196.50	D028300	M1	0.00	<0.005	0.001
198.00	198.00	D028303	K	0.00	1.135	1.135
211.50	213.00	D028313	D028312	1.50	0.075	0.075
225.00	225.00	D028323	L	0.00	2.250	2.250
238.50	240.00	D028333	D028332	1.50	0.036	0.036
247.50	247.50	D028340	M1	0.00	<0.005	0.001
250.50	250.50	D028343	M	0.00	3.170	3.170
264.00	265.50	D028353	D028352	1.50	0.010	0.010
277.50	277.50	D028363	J	0.00	0.745	0.745

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-238</b>	Titre minier :	Section :	629900
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley	Lot :		
Décrit par : F. Larouche	Du : 2010-05-17	Date de description :	2010-07-01
	Au : 2010-05-22		

Collet

Azimut : 180.00°  
 Plongée : -73.00°  
 Longueur : 335.00 m

UTM

Est	629 899.8
Nord	5 374 298.8
Élévation	279.8

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	342.90°	-74.50°	Oui
Reflex	8.00	344.30°	-73.60°	Oui
Reflex	11.00	209.30°	-73.50°	Oui
Reflex	14.00	330.50°	-73.10°	Oui
Reflex	17.00	348.10°	-72.00°	Oui
Reflex	20.00	36.70°	-71.10°	Oui
Reflex	23.00	166.70°	-70.80°	Oui
Reflex	26.00	23.10°	-71.20°	Oui
Reflex	29.00	339.40°	-71.90°	Oui
Reflex	32.00	333.60°	-72.40°	Oui
Reflex	35.00	338.80°	-72.50°	Oui

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	219.30°	-72.30°	Oui
Reflex	41.00	318.80°	-72.10°	Oui
Reflex	44.00	318.70°	-72.20°	Oui
Reflex	47.00	309.30°	-72.20°	Oui
Reflex	50.00	178.20°	-72.10°	Oui
Reflex	53.00	177.50°	-71.60°	Non
Reflex	56.00	178.90°	-72.10°	Non
Reflex	59.00	178.20°	-72.90°	Non
Reflex	62.00	179.10°	-71.80°	Non
Reflex	65.00	179.30°	-71.20°	Non
Reflex	68.00	178.70°	-71.80°	Non
Reflex	71.00	178.90°	-71.70°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	183.30°	-67.60°	Non	Reflex	173.00	178.60°	-68.40°	Non
Reflex	77.00	179.20°	-71.50°	Non	Reflex	176.00	178.40°	-68.10°	Non
Reflex	80.00	179.40°	-71.40°	Non	Reflex	179.00	178.50°	-68.00°	Non
Reflex	83.00	218.00°	-57.20°	Oui	Reflex	182.00	178.00°	-67.90°	Non
Reflex	86.00	180.30°	-70.90°	Non	Reflex	185.00	177.90°	-67.70°	Non
Reflex	89.00	179.90°	-70.80°	Non	Reflex	188.00	177.80°	-67.60°	Non
Reflex	92.00	179.90°	-71.00°	Non	Reflex	191.00	178.00°	-67.60°	Non
Reflex	95.00	180.00°	-70.90°	Non	Reflex	194.00	177.70°	-67.50°	Non
Reflex	98.00	179.90°	-70.90°	Non	Reflex	197.00	178.10°	-67.50°	Non
Reflex	101.00	173.60°	-71.10°	Non	Reflex	200.00	177.90°	-67.40°	Non
Reflex	104.00	179.70°	-70.70°	Non	Reflex	203.00	178.00°	-67.30°	Non
Reflex	107.00	179.60°	-70.70°	Non	Reflex	206.00	178.10°	-67.20°	Non
Reflex	110.00	183.90°	-66.60°	Oui	Reflex	209.00	177.40°	-67.10°	Non
Reflex	113.00	179.90°	-70.40°	Non	Reflex	212.00	177.50°	-67.10°	Non
Reflex	116.00	179.70°	-70.30°	Non	Reflex	215.00	177.60°	-67.20°	Non
Reflex	119.00	179.90°	-70.20°	Non	Reflex	218.00	178.10°	-67.20°	Non
Reflex	122.00	179.40°	-70.00°	Non	Reflex	221.00	178.00°	-67.10°	Non
Reflex	125.00	179.50°	-69.90°	Non	Reflex	224.00	177.80°	-67.10°	Non
Reflex	128.00	179.70°	-69.80°	Non	Reflex	227.00	178.00°	-67.00°	Non
Reflex	131.00	179.70°	-69.80°	Non	Reflex	230.00	178.30°	-67.00°	Non
Reflex	134.00	179.90°	-69.70°	Non	Reflex	233.00	178.50°	-66.80°	Non
Reflex	137.00	180.30°	-69.60°	Non	Reflex	236.00	178.80°	-67.00°	Non
Reflex	140.00	179.50°	-69.60°	Non	Reflex	239.00	178.70°	-66.70°	Non
Reflex	143.00	179.60°	-69.50°	Non	Reflex	242.00	178.80°	-66.70°	Non
Reflex	146.00	179.50°	-69.40°	Non	Reflex	245.00	178.50°	-66.80°	Non
Reflex	149.00	178.20°	-69.10°	Non	Reflex	248.00	178.40°	-66.80°	Non
Reflex	152.00	178.20°	-69.00°	Non	Reflex	251.00	178.30°	-66.80°	Non
Reflex	155.00	179.00°	-69.00°	Non	Reflex	254.00	178.30°	-66.80°	Non
Reflex	158.00	178.40°	-69.00°	Non	Reflex	257.00	178.30°	-66.70°	Non
Reflex	161.00	178.30°	-68.80°	Non	Reflex	260.00	178.30°	-66.70°	Non
Reflex	164.00	178.10°	-68.90°	Non	Reflex	263.00	178.20°	-66.70°	Non
Reflex	167.00	178.10°	-68.60°	Non	Reflex	266.00	178.00°	-66.70°	Non
Reflex	170.00	178.50°	-68.50°	Non	Reflex	269.00	178.30°	-66.70°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	178.10°	-66.70°	Non					
Reflex	275.00	178.00°	-66.80°	Non					
Reflex	278.00	178.30°	-66.80°	Non					
Reflex	281.00	178.10°	-66.70°	Non					
Reflex	284.00	178.10°	-66.70°	Non					
Reflex	287.00	178.00°	-66.60°	Non					
Reflex	290.00	177.60°	-66.60°	Non					
Reflex	293.00	177.40°	-66.50°	Non					
Reflex	296.00	177.50°	-66.50°	Non					
Reflex	299.00	177.30°	-66.30°	Non					
Reflex	302.00	177.10°	-66.30°	Non					
Reflex	305.00	177.10°	-66.20°	Non					
Reflex	308.00	177.30°	-66.10°	Non					
Reflex	311.00	177.50°	-66.00°	Non					
Reflex	314.00	177.60°	-65.90°	Non					
Reflex	317.00	177.70°	-65.90°	Non					
Reflex	320.00	178.10°	-65.70°	Non					
Reflex	323.00	178.20°	-65.50°	Non					
Reflex	326.00	178.40°	-65.50°	Non					
Reflex	329.00	178.50°	-65.50°	Non					
Reflex	332.00	178.60°	-65.40°	Non					
Reflex	335.00	178.60°	-65.30°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	46.30	MT						
		<b>Mort-terrain</b>						
46.30	87.30	MS						
		<b>Mudstone</b>						
		Sédiments, gris verdâtre, grains fins, faib. alt. (CH), partiellement faib. alt. (CB), un litage à 60° AC est visible, plusieurs vns de Qz-Cb et aussi de graphite se sont mises en place suivant ce litage, Tr. à 1 % Py diss.						
46.30	117.60	CH	46.30	47.40	D036001	1.10	<0.005	0.001
		<b>Chloriteux</b>	47.40	48.50	D036002	1.10	<0.005	0.001
		Faib. alt. (CH)	48.50	50.00	D036003	1.50	0.006	0.006
			50.00	51.50	D036004	1.50	<0.005	0.001
			51.50	53.00	D036005	1.50	<0.005	0.001
			53.00	54.50	D036006	1.50	<0.005	0.001
			54.50	56.00	D036007	1.50	<0.005	0.001
			56.00	57.50	D036009	1.50	<0.005	0.001
			57.50	59.00	D036010	1.50	<0.005	0.001
			59.00	60.50	D036011	1.50	<0.005	0.001
			60.50	62.00	D036012	1.50	<0.005	0.001
			62.00	63.50	D036013	1.50	<0.005	0.001
			63.50	65.00	D036014	1.50	<0.005	0.001
			65.00	66.50	D036015	1.50	<0.005	0.001
			66.50	68.00	D036016	1.50	<0.005	0.001
			68.00	69.50	D036017	1.50	<0.005	0.001
			69.50	71.00	D036019	1.50	<0.005	0.001
			71.00	72.50	D036021	1.50	<0.005	0.001
			72.50	74.00	D036022	1.50	<0.005	0.001
			74.00	75.50	D036023	1.50	0.007	0.007
			75.50	77.00	D036024	1.50	<0.005	0.001
			77.00	78.50	D036025	1.50	<0.005	0.001
			78.50	80.00	D036026	1.50	<0.005	0.001
			80.00	81.50	D036027	1.50	<0.005	0.001
			81.50	83.00	D036029	1.50	<0.005	0.001
			83.00	84.50	D036030	1.50	<0.005	0.001
			84.50	86.00	D036031	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
87.30	106.90	GA <b>Gabbro 60°</b> Gabbro, grenue, vert pâle, faib. alt. (CH), partiellement faib. alt. (CB), qqes vnls de Qz-Cb, présence de portions décimétriques cisailées, présence de leucoxènes, rares Tr. Py	86.00	87.30	D036032	1.30	<0.005		0.001
			87.30	89.00	D036033	1.70	<0.005		0.001
			89.00	90.50	D036034	1.50	<0.005		0.001
			90.50	92.00	D036035	1.50	<0.005		0.001
			92.00	93.50	D036036	1.50	<0.005		0.001
			93.50	95.00	D036037	1.50	0.006		0.006
			95.00	96.50	D036039	1.50	<0.005		0.001
			96.50	98.00	D036040	1.50	<0.005		0.001
			98.00	99.50	D036041	1.50	0.006		0.006
			99.50	101.00	D036042	1.50	<0.005		0.001
			101.00	102.50	D036043	1.50	<0.005		0.001
			102.50	104.00	D036044	1.50	<0.005		0.001
			104.00	105.50	D036045	1.50	<0.005		0.001
106.90	117.60	MS <b>Mudstone</b> Sédiments, gris verdâtre, grains fins, faib. alt. (CH), partiellement faib. alt. (CB), un litage à 50° AC est visible, plusieurs vnls de Qz-Cb et aussi de graphite se sont mises en place suivant ce litage, Tr. à 1 % Py diss.	105.50	106.90	D036046	1.40	0.008		0.008
			106.90	108.50	D036047	1.60	<0.005		0.001
			108.50	110.00	D036049	1.50	<0.005		0.001
			110.00	111.50	D036050	1.50	<0.005		0.001
			111.50	113.00	D036051	1.50	<0.005		0.001
			113.00	114.50	D036052	1.50	<0.005		0.001
			114.50	116.00	D036053	1.50	0.006		0.006
117.60	159.90	GA <b>Gabbro 55°</b> Gabbro, grenue, vert pâle, fort. alt. (CB), faib. alt. (CH), qqes vnls de Qz-Cb, présence de leucoxènes, rares Tr. Py	116.00	117.60	D036054	1.60	<0.005		0.001
			117.60	171.60					
117.60	208.30	CIS <b>Cisaillement 50°</b> Faib. à moy. cis. à 50° AC	117.60	119.00	D036055	1.40	0.005		0.005
			119.00	120.50	D036056	1.50	0.005		0.005
117.60	208.30	CIS <b>Cisaillement 50°</b> Faib. à moy. cis. à 50° AC	120.50	122.00	D036057	1.50	0.011		0.011
			122.00	123.50	D036059	1.50	<0.005		0.001
			123.50	125.00	D036061	1.50	<0.005		0.001
			125.00	126.50	D036062	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			126.50	128.00	D036063	1.50	<0.005		0.001
			128.00	129.50	D036064	1.50	<0.005		0.001
			129.50	131.00	D036065	1.50	<0.005		0.001
			131.00	132.50	D036066	1.50	<0.005		0.001
			132.50	134.00	D036067	1.50	<0.005		0.001
			134.00	135.50	D036069	1.50	<0.005		0.001
			135.50	137.00	D036070	1.50	<0.005		0.001
			137.00	138.50	D036071	1.50	<0.005		0.001
			138.50	140.00	D036072	1.50	<0.005		0.001
			140.00	141.50	D036073	1.50	<0.005		0.001
			141.50	143.00	D036074	1.50	0.013		0.013
			143.00	144.50	D036075	1.50	<0.005		0.001
			144.50	146.00	D036076	1.50	<0.005		0.001
			146.00	147.50	D036077	1.50	<0.005		0.001
			147.50	149.00	D036079	1.50	<0.005		0.001
			149.00	150.50	D036080	1.50	<0.005		0.001
			150.50	152.00	D036081	1.50	<0.005		0.001
			152.00	153.50	D036082	1.50	<0.005		0.001
			153.50	155.00	D036083	1.50	<0.005		0.001
			155.00	156.50	D036084	1.50	<0.005		0.001
			156.50	158.00	D036085	1.50	<0.005		0.001
			158.00	159.00	D036086	1.00	<0.005		0.001
			159.00	159.90	D036087	0.90	<0.005		0.001
159.90	171.60	MS	159.90	161.00	D036089	1.10	0.021		0.021
		<b>Mudstone 45°</b>	161.00	162.50	D036090	1.50	<0.005		0.001
		Sédiments, gris verdâtre (parfois vert pomme = épidote et/ou séricite), grains fins, moy. alt. (CB), faib. alt. (CH), un cisaillement à 45° AC est visible et masque tout litage, plusieurs vnl de Qz-Cb et aussi de graphite sont présentes, Tr. à 1 % Py diss. généralement (qqes bandes < 10 cm, 25 % Py)	162.50	164.00	D036091	1.50	0.012		0.012
			164.00	165.50	D036092	1.50	<0.005		0.001
			165.50	167.00	D036093	1.50	<0.005		0.001
			167.00	168.50	D036094	1.50	<0.005		0.001
			168.50	170.00	D036095	1.50	<0.005		0.001
			170.00	171.60	D036096	1.60	0.007		0.007
171.60	184.10	UM							
		<b>Ultramafite serpentinisée 45°</b>							
		Gris foncé (parfois verdâtre = chlorite), grains fins, rayable à l'ongle,							



Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
171.60	206.90	IN <b>Inaltéré</b>	présence de vnls de Tc-Cb, moy. cis. à 45° AC						
			171.60	173.00	D036097	1.40	0.039		0.039
			173.00	174.50	D036099	1.50	<0.005		0.001
			174.50	176.00	D036101	1.50	<0.005		0.001
			176.00	177.50	D036102	1.50	<0.005		0.001
			177.50	179.00	D036103	1.50	<0.005		0.001
			179.00	180.50	D036104	1.50	<0.005		0.001
			180.50	182.00	D036105	1.50	<0.005		0.001
			182.00	183.00	D036106	1.00	<0.005		0.001
			183.00	184.10	D036107	1.10	<0.005		0.001
184.10	206.90	UM; BRC <b>Ultramafite serpentinisée; Brèche de coulée</b> Gris foncé verdâtre, grains fins, il s'agit d'une litho. se situant dans un couloir de déformation et se composant de matériel sédimentaire fragmentaire, dans un matériel matriciel étant ultramafique, partiellement rayable à l'ongle, présence de vnls de Tc-Cb, schistosité de 40° AC	184.10	185.00	D036109	0.90	<0.005		0.001
			185.00	186.50	D036110	1.50	<0.005		0.001
			186.50	188.00	D036111	1.50	<0.005		0.001
			188.00	189.50	D036112	1.50	<0.005		0.001
			189.50	191.00	D036113	1.50	<0.005		0.001
			191.00	192.50	D036114	1.50	<0.005		0.001
			192.50	194.00	D036115	1.50	<0.005		0.001
			194.00	195.50	D036116	1.50	<0.005		0.001
			195.50	197.00	D036117	1.50	<0.005		0.001
			197.00	198.50	D036119	1.50	<0.005		0.001
			198.50	200.00	D036120	1.50	<0.005		0.001
			200.00	201.50	D036121	1.50	<0.005		0.001
			201.50	203.00	D036122	1.50	<0.005		0.001
203.00	204.50	D036123	1.50	<0.005		0.001			
204.50	206.00	D036124	1.50	<0.005		0.001			
206.00	206.90	D036125	0.90	<0.005		0.001			
206.90	208.30	MS <b>Mudstone</b> Sédiments, gris verdâtre, grains fins, moy. alt. (CB), faib. alt. (CH), un cisaillement à 45° AC est visible, plusieurs vnls de Qz-Cb et aussi de graphite sont présentes, Tr. à 1 % Py diss.							
206.90	208.30	CB <b>Carbonaté</b> Moy. alt. (CB)	206.90	208.30	D036126	1.40	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
208.30	214.70	UM; BRC <b>Ultramaïfite serpentinisée; Brèche de coulée</b> Idem à: de 184.1 à 206.9 m						
208.30	214.70	IN <b>Inaltéré</b>	208.30	209.10	D036127	0.80	<0.005	0.001
			209.10	210.50	D036129	1.40	<0.005	0.001
			210.50	211.90	D036130	1.40	<0.005	0.001
208.30	211.90	FAI; CIS <b>Faille 45°; Cisaillement</b> Cis. fort. avec qqes zones de faille comportant de la boue, présences de plusieurs mcx quartzeux						
211.90	220.20	CIS <b>Cisaillement 40°</b> Faib. à moy. cis. à 40° AC	211.90	213.30	D036131	1.40	<0.005	0.001
			213.30	214.70	D036132	1.40	0.009	0.009
214.70	236.60	MS <b>Mudstone</b> Idem à: de 106.9 à 117.6 m						
214.70	236.60	CH <b>Chloriteux</b> Faib. alt. (CH)	214.70	216.40	D036133	1.70	0.010	0.010
			216.40	218.00	D036134	1.60	0.006	0.006
			218.00	219.50	D036135	1.50	0.007	0.007
			219.50	221.00	D036136	1.50	<0.005	0.001
			221.00	222.50	D036137	1.50	0.014	0.014
			222.50	224.00	D036139	1.50	0.006	0.006
			224.00	225.50	D036141	1.50	0.009	0.009
			225.50	227.00	D036142	1.50	0.008	0.008
			227.00	228.50	D036143	1.50	<0.005	0.001
			228.50	230.00	D036144	1.50	0.008	0.008
			230.00	231.50	D036145	1.50	0.007	0.007
			231.50	233.00	D036146	1.50	<0.005	0.001
			233.00	234.50	D036147	1.50	0.005	0.005
			234.50	235.50	D036149	1.00	0.008	0.008
			235.50	236.60	D036150	1.10	0.005	0.005
236.60	247.40	UM; BRC <b>Ultramaïfite serpentinisée 20°; Brèche de coulée</b> Idem à: de 184.1 à 206.9 m						
236.60	253.50	IN <b>Inaltéré</b>						

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
236.60	253.50	CIS <b>Cisaillement 40°</b> Faib. à moy. cis. à 40° AC	236.60	237.50	D036151	0.90	0.010		0.010
			237.50	239.00	D036152	1.50	<0.005		0.001
			239.00	240.50	D036153	1.50	<0.005		0.001
			240.50	242.00	D036154	1.50	<0.005		0.001
			242.00	243.50	D036155	1.50	0.005		0.005
			243.50	245.00	D036156	1.50	<0.005		0.001
			245.00	246.20	D036157	1.20	<0.005		0.001
			246.20	247.40	D036159	1.20	<0.005		0.001
247.40	253.50	UM <b>Ultramafite serpentinisée 20°</b> Gris foncé, grains fins, rayable à l'ongle, présence de vnls de Tc-Cb, moy. cis. à 35° AC	247.40	249.00	D036160	1.60	<0.005		0.001
			249.00	250.50	D036161	1.50	<0.005		0.001
			250.50	252.00	D036162	1.50	<0.005		0.001
			252.00	253.50	D036163	1.50	<0.005		0.001
253.50	256.10	MS <b>Mudstone</b> Sédiments, gris verdâtre, grains fins, faib. alt. (CH), un litage à 40° AC est visible, plusieurs vnls de Qz-Cb, Tr. Py diss.	253.50	254.80	D036164	1.30	<0.005		0.001
			254.80	256.10	D036165	1.30	<0.005		0.001
256.10	258.90	UM <b>Ultramafite serpentinisée 35°</b> Idem à: de 247.4 à 253.5 m	256.10	257.50	D036166	1.40	<0.005		0.001
			257.50	258.90	D036167	1.40	<0.005		0.001
258.90	335.00	GR <b>Grès</b> Sédiments, verdâtre, grains fins, faib. alt. (SR), un litage à 55° AC est visible, qqes vnls de Qz-Cb (surtout dans les vingt premiers mètres de la litho.), la séricite s'est mise en place sous forme de cheveux suivant le litage, Tr. Py diss., partiellement très faiblement plissé. De 323.0 à 335.0 m, il ya présence de jaspe (en une dizaine d'endroits).	258.90	260.00	D036169	1.10	<0.005		0.001
			260.00	261.50	D036170	1.50	<0.005		0.001
			261.50	263.00	D036171	1.50	<0.005		0.001
			263.00	264.50	D036172	1.50	<0.005		0.001
			264.50	266.00	D036173	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
265.60	266.00	QZVN	266.00	267.50	D036174	1.50	0.009		0.009
		<b>Veine de Quartz massive 75°</b> Vn QzCbCl, 1 % Py, 75° AC	267.50	269.00	D036175	1.50	0.126		0.126
268.40	268.80	QZVN	269.00	270.50	D036176	1.50	0.016		0.016
		<b>Veine de Quartz massive 40°</b> Vn QzCbCl, 1 % Py, 40° AC	270.50	272.00	D036177	1.50	0.064		0.064
			272.00	273.50	D036179	1.50	0.009		0.009
272.70	273.00	QZVN	273.50	275.00	D036181	1.50	0.006		0.006
		<b>Veine de Quartz massive 30°</b> Vn QzCb, Tr. Py, 30° AC	275.00	276.50	D036182	1.50	0.005		0.005
			276.50	278.00	D036183	1.50	0.009		0.009
			278.00	279.50	D036184	1.50	0.006		0.006
			279.50	281.00	D036185	1.50	0.005		0.005
			281.00	282.50	D036186	1.50	0.034		0.034
			282.50	284.00	D036187	1.50	0.020		0.020
			284.00	285.50	D036189	1.50	0.005		0.005
			285.50	287.00	D036190	1.50	0.007		0.007
			287.00	288.50	D036191	1.50	0.012		0.012
			288.50	290.00	D036192	1.50	0.005		0.005
			290.00	291.50	D036193	1.50	0.007		0.007
			291.50	293.00	D036194	1.50	<0.005		0.001
			293.00	294.50	D036195	1.50	<0.005		0.001
			294.50	296.00	D036196	1.50	0.007		0.007
			296.00	297.50	D036197	1.50	0.007		0.007
			297.50	299.00	D036199	1.50	0.008		0.008
	299.00	300.50	D036200	1.50	0.006		0.006		
	300.50	302.00	D036201	1.50	0.007		0.007		
	302.00	303.50	D036202	1.50	0.007		0.007		
	303.50	305.00	D036203	1.50	0.006		0.006		
	305.00	306.50	D036204	1.50	0.008		0.008		
	306.50	308.00	D036205	1.50	0.008		0.008		
	308.00	309.50	D036206	1.50	<0.005		0.001		
	309.50	311.00	D036207	1.50	0.015		0.015		
	311.00	312.50	D036209	1.50	0.005		0.005		
	312.50	314.00	D036210	1.50	<0.005		0.001		
	314.00	315.50	D036211	1.50	0.010		0.010		

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
322.30      335.00      CIS <b>Cisaillement 45°</b> Moy. cis. à 45° AC, des vnls de Cb se sont mises en place suivant ce cisaillement.	315.50	317.00	D036212	1.50	0.005		0.005
	317.00	318.50	D036213	1.50	0.008		0.008
	318.50	320.00	D036214	1.50	0.005		0.005
	320.00	321.50	D036215	1.50	0.008		0.008
	321.50	323.00	D036216	1.50	0.044		0.044
	323.00	324.50	D036217	1.50	0.006		0.006
	324.50	326.00	D036219	1.50	0.018		0.018
	326.00	327.50	D036221	1.50	0.029		0.029
	327.50	329.00	D036222	1.50	0.009		0.009
	329.00	330.50	D036223	1.50	0.052		0.052
	330.50	332.00	D036224	1.50	0.065		0.065
	332.00	333.50	D036225	1.50	0.071		0.071
	333.50	335.00	D036226	1.50	0.024		0.024
	335.00	Fin du sondage Nombre d'échantillons : 198 Nombre d'échantillons QAQC : 28 Longueur totale échantillonnée : 288.70					

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
54.50	56.00	D036008	D036007	1.50	<0.005	0.001
68.00	68.00	D036018	J	0.00	0.717	0.717
69.50	69.50	D036020	M1	0.00	<0.005	0.001
80.00	81.50	D036028	D036027	1.50	<0.005	0.001
93.50	93.50	D036038	K	0.00	1.025	1.025
106.90	108.50	D036048	D036047	1.60	<0.005	0.001
120.50	120.50	D036058	L	0.00	2.080	2.080
122.00	122.00	D036060	M1	0.00	<0.005	0.001
132.50	134.00	D036068	D036067	1.50	<0.005	0.001
146.00	146.00	D036078	M	0.00	2.930	2.930
159.00	159.90	D036088	D036087	0.90	<0.005	0.001
171.60	171.60	D036098	J	0.00	0.748	0.748
173.00	173.00	D036100	M1	0.00	<0.005	0.001
183.00	184.10	D036108	D036107	1.10	<0.005	0.001
195.50	195.50	D036118	K	0.00	0.992	0.992
208.30	209.10	D036128	D036127	0.80	<0.005	0.001
221.00	221.00	D036138	L	0.00	2.150	2.150
222.50	222.50	D036140	M1	0.00	<0.005	0.001
233.00	234.50	D036148	D036147	1.50	<0.005	0.001
245.00	245.00	D036158	M	0.00	2.760	2.760
257.50	258.90	D036168	D036167	1.40	<0.005	0.001
270.50	270.50	D036178	J	0.00	0.700	0.700
272.00	272.00	D036180	M1	0.00	<0.005	0.001
282.50	284.00	D036188	D036187	1.50	0.018	0.018
296.00	296.00	D036198	K	0.00	1.110	1.110
309.50	311.00	D036208	D036207	1.50	0.019	0.019
323.00	323.00	D036218	L	0.00	2.310	2.310
324.50	324.50	D036220	M1	0.00	<0.005	0.001

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-239**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-05-18

Date de description :

Au :                      2010-05-22

Collet

UTM

Azimut :                      0.00°  
 Plongée :                      -60.00°  
 Longueur :                      365.00 m

Est	631 099.9
Nord	5 374 399.8
Élévation	312.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	0.60°	-60.20°	Non
Reflex	8.00	0.10°	-60.30°	Non
Reflex	11.00	359.70°	-60.30°	Non
Reflex	14.00	359.20°	-60.20°	Non
Reflex	17.00	3.30°	-60.10°	Oui
Reflex	20.00	359.50°	-59.90°	Non
Reflex	23.00	0.50°	-59.60°	Non
Reflex	26.00	1.20°	-59.60°	Non
Reflex	29.00	1.60°	-59.40°	Non
Reflex	32.00	358.90°	-59.20°	Non
Reflex	35.00	0.30°	-59.00°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.40°	-58.80°	Non
Reflex	41.00	359.80°	-58.60°	Non
Reflex	44.00	360.00°	-58.40°	Non
Reflex	47.00	0.30°	-58.20°	Non
Reflex	50.00	0.40°	-58.10°	Non
Reflex	53.00	0.50°	-58.00°	Non
Reflex	56.00	1.00°	-57.90°	Non
Reflex	59.00	0.80°	-57.90°	Non
Reflex	62.00	2.10°	-57.80°	Non
Reflex	65.00	3.80°	-57.70°	Non
Reflex	68.00	4.30°	-57.60°	Non
Reflex	71.00	3.90°	-57.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	3.30°	-57.50°	Non	Reflex	173.00	2.80°	-56.20°	Non
Reflex	77.00	1.70°	-57.40°	Non	Reflex	176.00	3.20°	-56.20°	Non
Reflex	80.00	1.40°	-57.40°	Non	Reflex	179.00	2.50°	-56.20°	Non
Reflex	83.00	2.50°	-57.40°	Non	Reflex	182.00	1.90°	-56.10°	Non
Reflex	86.00	2.40°	-57.40°	Non	Reflex	185.00	2.40°	-56.10°	Non
Reflex	89.00	2.40°	-57.40°	Non	Reflex	188.00	2.70°	-56.00°	Non
Reflex	92.00	2.70°	-57.30°	Non	Reflex	191.00	2.70°	-56.00°	Non
Reflex	95.00	3.60°	-57.30°	Non	Reflex	194.00	3.50°	-56.00°	Non
Reflex	98.00	3.20°	-57.20°	Non	Reflex	197.00	2.70°	-56.00°	Non
Reflex	101.00	3.40°	-57.20°	Non	Reflex	200.00	2.80°	-55.90°	Non
Reflex	104.00	4.00°	-57.10°	Non	Reflex	203.00	2.80°	-55.90°	Non
Reflex	107.00	3.80°	-57.10°	Non	Reflex	206.00	4.00°	-56.00°	Non
Reflex	110.00	4.00°	-57.00°	Non	Reflex	209.00	4.40°	-55.90°	Non
Reflex	113.00	4.70°	-57.00°	Non	Reflex	212.00	4.30°	-55.90°	Non
Reflex	116.00	4.40°	-57.00°	Non	Reflex	215.00	3.90°	-55.90°	Non
Reflex	119.00	3.50°	-57.00°	Non	Reflex	218.00	4.30°	-56.00°	Non
Reflex	122.00	3.10°	-56.90°	Non	Reflex	221.00	4.60°	-55.90°	Non
Reflex	125.00	1.40°	-56.80°	Non	Reflex	224.00	4.90°	-55.90°	Non
Reflex	128.00	0.60°	-56.80°	Non	Reflex	227.00	5.10°	-55.90°	Non
Reflex	131.00	0.40°	-56.60°	Non	Reflex	230.00	5.30°	-55.90°	Non
Reflex	134.00	0.30°	-56.60°	Non	Reflex	233.00	5.50°	-55.90°	Non
Reflex	137.00	0.40°	-56.50°	Non	Reflex	236.00	5.60°	-55.80°	Non
Reflex	140.00	0.30°	-56.40°	Non	Reflex	239.00	6.10°	-55.70°	Non
Reflex	143.00	0.90°	-56.30°	Non	Reflex	242.00	6.00°	-55.80°	Non
Reflex	146.00	4.80°	-56.30°	Non	Reflex	245.00	7.50°	-55.70°	Non
Reflex	149.00	4.50°	-56.30°	Non	Reflex	248.00	7.30°	-55.70°	Non
Reflex	152.00	3.20°	-56.30°	Non	Reflex	251.00	7.50°	-55.70°	Non
Reflex	155.00	4.00°	-56.30°	Non	Reflex	254.00	7.40°	-55.60°	Non
Reflex	158.00	3.30°	-56.20°	Non	Reflex	257.00	3.50°	-55.60°	Oui
Reflex	161.00	5.40°	-56.20°	Oui	Reflex	260.00	7.30°	-55.50°	Non
Reflex	164.00	4.70°	-56.20°	Non	Reflex	263.00	8.10°	-55.50°	Non
Reflex	167.00	4.00°	-56.20°	Non	Reflex	266.00	7.70°	-55.40°	Non
Reflex	170.00	4.40°	-56.20°	Non	Reflex	269.00	9.70°	-55.40°	Non



Corporation Minière Osisko Div. Exploration

Déviaton

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	6.60°	-55.40°	Non					
Reflex	275.00	6.90°	-55.40°	Non					
Reflex	278.00	5.50°	-55.30°	Non					
Reflex	281.00	3.40°	-55.20°	Non					
Reflex	284.00	3.40°	-55.30°	Non					
Reflex	287.00	6.20°	-55.20°	Non					
Reflex	290.00	6.20°	-55.20°	Non					
Reflex	293.00	5.60°	-55.20°	Non					
Reflex	296.00	3.60°	-55.10°	Oui					
Reflex	299.00	6.90°	-55.10°	Non					
Reflex	302.00	6.60°	-55.10°	Non					
Reflex	305.00	7.70°	-55.00°	Non					
Reflex	308.00	6.30°	-54.90°	Non					
Reflex	311.00	6.50°	-54.90°	Non					
Reflex	314.00	6.40°	-54.90°	Non					
Reflex	317.00	6.40°	-54.80°	Non					
Reflex	320.00	6.40°	-54.70°	Non					
Reflex	323.00	6.40°	-54.70°	Non					
Reflex	326.00	6.50°	-54.70°	Non					
Reflex	329.00	6.50°	-54.70°	Non					
Reflex	332.00	6.60°	-54.60°	Non					
Reflex	335.00	7.50°	-54.50°	Non					
Reflex	338.00	6.80°	-54.40°	Non					
Reflex	341.00	6.60°	-54.40°	Non					
Reflex	344.00	4.00°	-54.30°	Oui					
Reflex	347.00	8.10°	-54.30°	Non					
Reflex	350.00	8.50°	-54.30°	Non					
Reflex	353.00	9.00°	-54.20°	Non					
Reflex	356.00	6.90°	-54.10°	Non					
Reflex	359.00	6.50°	-54.00°	Non					
Reflex	362.00	6.50°	-53.80°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
0.00	26.50	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite à grains fins avec passage porphyrique Xmm.	0.00	1.50	D018653	1.50	0.103		0.103			
			1.50	3.00	D018654	1.50	0.111		0.111			
			3.00	4.50	D018655	1.50	0.382		0.382			
			4.50	6.00	D018656	1.50	0.121		0.121			
			6.00	7.50	D018658	1.50	0.133		0.133			
			7.50	9.00	D018659	1.50	0.048		0.048			
			9.00	10.50	D018660	1.50	0.046		0.046			
			10.50	12.00	D018661	1.50	0.188		0.188			
			12.00	13.50	D018663	1.50	0.126		0.126			
			13.50	15.00	D018664	1.50	0.099		0.099			
			15.00	16.50	D018665	1.50	0.065		0.065			
			16.50	18.00	D018666	1.50	0.056		0.056			
			18.00	19.50	D018668	1.50	0.334		0.334			
			19.50	21.00	D018669	1.50	1.120		1.120			
			21.00	22.50	D018670	1.50	6.590		6.590			
			22.50	24.00	D018671	1.50	2.710		2.710			
			24.00	25.50	D018672	1.50	0.039		0.039			
			25.50	26.50	D018673	1.00	0.134		0.134			
			26.50	44.00	GA <b>Gabbro</b> Gabbro, microgrenue avec phénocristaux Xmm.	26.50	28.00	D018674	1.50	<0.005		0.001
						28.00	29.50	D018675	1.50	<0.005		0.001
29.50	31.00	D018676				1.50	0.191		0.191			
31.00	32.50	D018678				1.50	<0.005		0.001			
32.50	34.00	D018679				1.50	<0.005		0.001			
34.00	35.50	D018680				1.50	0.020		0.020			
35.50	37.00	D018681				1.50	<0.005		0.001			
37.00	38.50	D018682				1.50	<0.005		0.001			
38.50	40.00	D018683				1.50	<0.005		0.001			
40.00	41.50	D018684				1.50	<0.005		0.001			
44.00	365.00	SY; FIN; POR <b>Syénite; Grains fins; Porphyrique</b> Syénite, à grains fins, passage porphyrique à phénocristaux Xmm à rarement Xcm.	41.50	43.00	D018685	1.50	<0.005		0.001			
			43.00	44.00	D018686	1.00	<0.005		0.001			
			44.00	45.50	D018688	1.50	0.053		0.053			
			45.50	47.00	D018689	1.50	0.008		0.008			
			47.00	48.50	D018690	1.50	0.094		0.094			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	48.50	50.00	D018691	1.50	0.449		0.449
	50.00	51.50	D018692	1.50	0.516		0.516
	51.50	53.00	D018693	1.50	0.064		0.064
	53.00	54.50	D018694	1.50	0.019		0.019
	54.50	56.00	D018695	1.50	<0.005		0.001
	56.00	57.50	D018696	1.50	0.015		0.015
	57.50	59.00	D018698	1.50	<0.005		0.001
	59.00	60.50	D018699	1.50	0.006		0.006
	60.50	62.00	D018700	1.50	0.019		0.019
	62.00	63.50	D018701	1.50	0.007		0.007
	63.50	65.00	D018703	1.50	0.116		0.116
	65.00	66.50	D018704	1.50	0.012		0.012
	66.50	68.00	D018705	1.50	0.803		0.803
	68.00	69.50	D018706	1.50	0.009		0.009
	69.50	71.00	D018708	1.50	0.046		0.046
	71.00	72.50	D018709	1.50	0.032		0.032
	72.50	74.00	D018710	1.50	0.043		0.043
	74.00	75.50	D018711	1.50	0.149		0.149
	75.50	77.00	D018712	1.50	<0.005		0.001
	77.00	78.50	D018713	1.50	0.155		0.155
	78.50	80.00	D018714	1.50	0.011		0.011
	80.00	81.50	D018715	1.50	<0.005		0.001
	81.50	83.00	D018716	1.50	<0.005		0.001
	83.00	84.50	D018718	1.50	<0.005		0.001
	84.50	86.00	D018719	1.50	<0.005		0.001
	86.00	87.50	D018720	1.50	<0.005		0.001
	87.50	89.00	D018721	1.50	<0.005		0.001
	89.00	90.50	D018722	1.50	0.005		0.005
	90.50	92.00	D018723	1.50	0.196		0.196
	92.00	93.50	D018724	1.50	0.023		0.023
	93.50	95.00	D018725	1.50	<0.005		0.001
	95.00	96.50	D018726	1.50	0.008		0.008
	96.50	98.00	D018728	1.50	0.007		0.007

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	98.00	99.50	D018729	1.50	<0.005		0.001
	99.50	101.00	D018730	1.50	<0.005		0.001
	101.00	102.50	D018731	1.50	0.007		0.007
	102.50	104.00	D018732	1.50	0.048		0.048
	104.00	105.50	D018733	1.50	<0.005		0.001
	105.50	107.00	D018734	1.50	<0.005		0.001
	107.00	108.50	D018735	1.50	<0.005		0.001
	108.50	110.00	D018736	1.50	<0.005		0.001
	110.00	111.50	D018738	1.50	0.005		0.005
	111.50	113.00	D018739	1.50	0.041		0.041
	113.00	114.50	D018740	1.50	0.131		0.131
	114.50	116.00	D018741	1.50	0.007		0.007
	116.00	117.50	D018743	1.50	0.186		0.186
	117.50	119.00	D018744	1.50	0.364		0.364
	119.00	120.50	D018745	1.50	<0.005		0.001
	120.50	122.00	D018746	1.50	<0.005		0.001
	122.00	123.50	D018748	1.50	<0.005		0.001
	123.50	125.00	D018749	1.50	<0.005		0.001
	125.00	126.50	D018750	1.50	<0.005		0.001
	126.50	128.00	D018751	1.50	<0.005		0.001
	128.00	129.50	D018752	1.50	<0.005		0.001
	129.50	131.00	D018753	1.50	<0.005		0.001
	131.00	132.50	D018754	1.50	<0.005		0.001
	132.50	134.00	D018755	1.50	<0.005		0.001
	134.00	135.50	D018756	1.50	<0.005		0.001
	135.50	137.00	D018758	1.50	<0.005		0.001
	137.00	138.50	D018759	1.50	0.231		0.231
	138.50	140.00	D018760	1.50	0.185		0.185
	140.00	141.50	D018761	1.50	0.259		0.259
	141.50	143.00	D018762	1.50	0.197		0.197
	143.00	144.50	D018763	1.50	0.176		0.176
	144.50	146.00	D018764	1.50	0.011		0.011
	146.00	147.50	D018765	1.50	0.838		0.838

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	147.50	149.00	D018766	1.50	0.548		0.548
	149.00	150.50	D018768	1.50	<0.005		0.001
	150.50	152.00	D018769	1.50	<0.005		0.001
	152.00	153.50	D018770	1.50	<0.005		0.001
	153.50	155.00	D018771	1.50	<0.005		0.001
	155.00	156.50	D018772	1.50	<0.005		0.001
	156.50	158.00	D018773	1.50	0.005		0.005
	158.00	159.50	D018774	1.50	0.052		0.052
	159.50	161.00	D018775	1.50	0.879		0.879
	161.00	162.50	D018776	1.50	0.183		0.183
	162.50	164.00	D018778	1.50	<0.005		0.001
	164.00	165.50	D018779	1.50	0.051		0.051
	165.50	167.00	D018780	1.50	<0.005		0.001
	167.00	168.50	D018781	1.50	<0.005		0.001
	168.50	170.00	D018783	1.50	<0.005		0.001
	170.00	171.50	D018784	1.50	<0.005		0.001
	171.50	173.00	D018785	1.50	<0.005		0.001
	173.00	174.50	D018786	1.50	0.011		0.011
	174.50	176.00	D018788	1.50	<0.005		0.001
	176.00	177.50	D018789	1.50	0.010		0.010
	177.50	179.00	D018790	1.50	0.006		0.006
	179.00	180.50	D018791	1.50	<0.005		0.001
	180.50	182.00	D018792	1.50	<0.005		0.001
	182.00	183.50	D018793	1.50	<0.005		0.001
	183.50	185.00	D018794	1.50	<0.005		0.001
	185.00	186.50	D018795	1.50	<0.005		0.001
	186.50	188.00	D018796	1.50	<0.005		0.001
	188.00	189.50	D018798	1.50	0.047		0.047
	189.50	191.00	D018799	1.50	0.028		0.028
	191.00	192.50	D018800	1.50	0.022		0.022
	192.50	194.00	D018801	1.50	<0.005		0.001
	194.00	195.50	D018803	1.50	0.010		0.010
	195.50	197.00	D018804	1.50	0.010		0.010

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.00	198.50	D018805	1.50	0.005		0.005
	198.50	200.00	D018806	1.50	0.609		0.609
	200.00	201.50	D018808	1.50	0.012		0.012
	201.50	203.00	D018809	1.50	0.202		0.202
	203.00	204.50	D018810	1.50	0.156		0.156
	204.50	206.00	D018811	1.50	0.053		0.053
	206.00	207.50	D018812	1.50	0.798		0.798
	207.50	209.00	D018813	1.50	0.089		0.089
	209.00	210.50	D018814	1.50	0.152		0.152
	210.50	212.00	D018815	1.50	0.016		0.016
	212.00	213.50	D018816	1.50	0.012		0.012
	213.50	215.00	D018818	1.50	0.012		0.012
	215.00	216.50	D018819	1.50	0.036		0.036
	216.50	218.00	D018820	1.50	0.085		0.085
	218.00	219.50	D018821	1.50	0.017		0.017
	219.50	221.00	D018822	1.50	<0.005		0.001
	221.00	222.50	D018823	1.50	0.014		0.014
	222.50	224.00	D018824	1.50	<0.005		0.001
	224.00	225.50	D018825	1.50	0.005		0.005
	225.50	227.00	D018826	1.50	<0.005		0.001
	227.00	228.50	D018828	1.50	0.007		0.007
	228.50	230.00	D018829	1.50	<0.005		0.001
	230.00	231.50	D018830	1.50	<0.005		0.001
	231.50	233.00	D018831	1.50	<0.005		0.001
	233.00	234.50	D018832	1.50	<0.005		0.001
	234.50	236.00	D018833	1.50	<0.005		0.001
	236.00	237.50	D018834	1.50	<0.005		0.001
	237.50	239.00	D018835	1.50	<0.005		0.001
	239.00	240.50	D018836	1.50	<0.005		0.001
	240.50	242.00	D018838	1.50	<0.005		0.001
	242.00	243.50	D018839	1.50	<0.005		0.001
	243.50	245.00	D018840	1.50	<0.005		0.001
	245.00	246.50	D018841	1.50	0.018		0.018

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.50	248.00	D018843	1.50	0.212		0.212
	248.00	249.50	D018844	1.50	0.475		0.475
	249.50	251.00	D018845	1.50	<0.005		0.001
	251.00	252.50	D018846	1.50	0.210		0.210
	252.50	254.00	D018848	1.50	0.372		0.372
	254.00	255.50	D018849	1.50	0.415		0.415
	255.50	257.00	D018850	1.50	0.188		0.188
	257.00	258.50	D018851	1.50	0.330		0.330
	258.50	260.00	D018852	1.50	0.072		0.072
	260.00	261.50	D018853	1.50	0.005		0.005
	261.50	263.00	D018854	1.50	0.018		0.018
	263.00	264.50	D018855	1.50	0.020		0.020
	264.50	266.00	D018856	1.50	0.174		0.174
	266.00	267.50	D018858	1.50	0.091		0.091
	267.50	269.00	D018859	1.50	0.065		0.065
	269.00	270.50	D018860	1.50	0.017		0.017
	270.50	272.00	D018861	1.50	0.033		0.033
	272.00	273.50	D018862	1.50	0.023		0.023
	273.50	275.00	D018863	1.50	0.013		0.013
	275.00	276.50	D018864	1.50	<0.005		0.001
	276.50	278.00	D018865	1.50	0.005		0.005
	278.00	279.50	D018866	1.50	0.144		0.144
	279.50	281.00	D018868	1.50	0.077		0.077
	281.00	282.50	D018869	1.50	0.092		0.092
	282.50	284.00	D018870	1.50	0.576		0.576
	284.00	285.50	D018871	1.50	1.220		1.220
	285.50	287.00	D018872	1.50	0.293		0.293
	287.00	288.50	D018873	1.50	0.214		0.214
	288.50	290.00	D018874	1.50	0.121		0.121
	290.00	291.50	D018875	1.50	0.169		0.169
	291.50	293.00	D018876	1.50	1.095		1.095
	293.00	294.50	D018878	1.50	0.192		0.192
	294.50	296.00	D018879	1.50	0.145		0.145

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.00	297.50	D018880	1.50	0.158		0.158
	297.50	299.00	D018881	1.50	0.556		0.556
	299.00	300.50	D018883	1.50	0.058		0.058
	300.50	302.00	D018884	1.50	0.274		0.274
	302.00	303.50	D018885	1.50	<0.005		0.001
	303.50	305.00	D018886	1.50	<0.005		0.001
	305.00	306.50	D018888	1.50	<0.005		0.001
	306.50	308.00	D018889	1.50	<0.005		0.001
	308.00	309.50	D018890	1.50	0.034		0.034
	309.50	311.00	D018891	1.50	<0.005		0.001
	311.00	312.50	D018892	1.50	<0.005		0.001
	312.50	314.00	D018893	1.50	<0.005		0.001
	314.00	315.50	D018894	1.50	0.026		0.026
	315.50	317.00	D018895	1.50	0.022		0.022
	317.00	318.50	D018896	1.50	0.007		0.007
	318.50	320.00	D018898	1.50	0.199		0.199
	320.00	321.50	D018899	1.50	0.013		0.013
	321.50	323.00	D018900	1.50	<0.005		0.001
	323.00	324.50	D018901	1.50	0.120		0.120
	324.50	326.00	D018902	1.50	0.399		0.399
	326.00	327.50	D018903	1.50	0.117		0.117
	327.50	329.00	D018904	1.50	0.028		0.028
	329.00	330.50	D018905	1.50	0.093		0.093
	330.50	332.00	D018906	1.50	0.010		0.010
	332.00	333.50	D018908	1.50	0.059		0.059
	333.50	335.00	D018909	1.50	0.036		0.036
	335.00	336.50	D018910	1.50	0.033		0.033
	336.50	338.00	D018911	1.50	0.013		0.013
	338.00	339.50	D018912	1.50	0.066		0.066
	339.50	341.00	D018913	1.50	0.150		0.150
	341.00	342.50	D018914	1.50	0.119		0.119
	342.50	344.00	D018915	1.50	0.025		0.025
	344.00	345.50	D018916	1.50	0.078		0.078



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D018918	1.50	0.090		0.090
	347.00	348.50	D018919	1.50	0.022		0.022
	348.50	350.00	D018920	1.50	0.519		0.519
	350.00	351.50	D018921	1.50	0.286		0.286
	351.50	353.00	D018923	1.50	<0.005		0.001
	353.00	354.50	D018924	1.50	<0.005		0.001
	354.50	356.00	D018925	1.50	0.025		0.025
	356.00	357.50	D018926	1.50	0.036		0.036
	357.50	359.00	D018928	1.50	0.331		0.331
	359.00	360.50	D018929	1.50	0.022		0.022
	360.50	362.00	D018930	1.50	0.060		0.060
	362.00	363.50	D018931	1.50	0.338		0.338
	363.50	365.00	D018932	1.50	0.043		0.043
365.00	Fin du sondage Nombre d'échantillons : 244 Nombre d'échantillons QAQC : 36 Longueur totale échantillonnée : 365.00						

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
4.50	6.00	D018657	D018656	1.50	0.314	0.314
10.50	10.50	D018662	M1	0.00	<0.005	0.001
16.50	16.50	D018667	J	0.00	0.778	0.778
29.50	31.00	D018677	D018676	1.50	0.208	0.208
43.00	43.00	D018687	K	0.00	1.175	1.175
56.00	57.50	D018697	D018696	1.50	0.012	0.012
62.00	62.00	D018702	M1	0.00	<0.005	0.001
68.00	68.00	D018707	L	0.00	2.190	2.190
81.50	83.00	D018717	D018716	1.50	<0.005	0.001
95.00	95.00	D018727	M	0.00	3.430	3.430
108.50	110.00	D018737	D018736	1.50	<0.005	0.001
114.50	114.50	D018742	M1	0.00	<0.005	0.001
120.50	120.50	D018747	J	0.00	0.622	0.622
134.00	135.50	D018757	D018756	1.50	<0.005	0.001
147.50	147.50	D018767	K	0.00	0.946	0.946
161.00	162.50	D018777	D018776	1.50	0.161	0.161
167.00	167.00	D018782	M1	0.00	<0.005	0.001
173.00	173.00	D018787	L	0.00	2.250	2.250
186.50	188.00	D018797	D018796	1.50	<0.005	0.001
192.50	192.50	D018802	M1	0.00	<0.005	0.001
198.50	198.50	D018807	J	0.00	0.781	0.781
212.00	213.50	D018817	D018816	1.50	0.022	0.022
225.50	225.50	D018827	K	0.00	0.955	0.955
239.00	240.50	D018837	D018836	1.50	<0.005	0.001
245.00	245.00	D018842	M1	0.00	<0.005	0.001
251.00	251.00	D018847	L	0.00	2.150	2.150
264.50	266.00	D018857	D018856	1.50	0.168	0.168
278.00	278.00	D018867	M	0.00	3.020	3.020
291.50	293.00	D018877	D018876	1.50	1.070	1.070
297.50	297.50	D018882	M1	0.00	<0.005	0.001
303.50	303.50	D018887	J	0.00	0.771	0.771
317.00	318.50	D018897	D018896	1.50	0.008	0.008
330.50	330.50	D018907	K	0.00	1.115	1.115

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
344.00	345.50	D018917	D018916	1.50	0.076	0.076
350.00	350.00	D018922	M1	0.00	<0.005	0.001
356.00	356.00	D018927	L	0.00	2.050	2.050

## Corporation Minière Osisko Div. Exploration

**Sondage :**      **BD10-240**

Titre minier :

Section :                      631100

Canton :

Niveau :

Foré par :              Bradley

Rang :

Place de travail :              Malartic

Décrit par :              David RUHARA

Lot :

Du :                      2010-05-22

Date de description :

Au :                      2010-05-29

Collet

UTM

Azimut :                      0.00°

Plongée :                      -60.00°

Longueur :                      452.00 m

Est                      631 099.8

Nord                      5 374 350.1

Élévation                      313.3

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	358.90°	-58.70°	Non
Reflex	8.00	358.70°	-58.40°	Non
Reflex	11.00	359.30°	-58.90°	Non
Reflex	14.00	359.80°	-58.90°	Non
Reflex	17.00	358.90°	-58.50°	Non
Reflex	20.00	359.20°	-58.50°	Non
Reflex	23.00	358.70°	-58.50°	Non
Reflex	26.00	358.90°	-58.50°	Non
Reflex	29.00	359.00°	-58.40°	Non
Reflex	32.00	358.90°	-58.50°	Non
Reflex	35.00	359.30°	-58.50°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	359.30°	-58.50°	Non
Reflex	41.00	359.60°	-58.60°	Non
Reflex	44.00	359.40°	-58.50°	Non
Reflex	47.00	359.70°	-58.60°	Non
Reflex	50.00	359.80°	-58.50°	Non
Reflex	53.00	359.80°	-58.60°	Non
Reflex	56.00	359.90°	-58.50°	Non
Reflex	59.00	360.00°	-58.50°	Non
Reflex	62.00	0.10°	-58.60°	Non
Reflex	65.00	0.10°	-58.60°	Non
Reflex	68.00	0.10°	-58.50°	Non
Reflex	71.00	0.20°	-58.60°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	0.50°	-58.70°	Non	Reflex	173.00	4.90°	-58.60°	Non
Reflex	77.00	0.50°	-58.70°	Non	Reflex	176.00	4.10°	-58.50°	Non
Reflex	80.00	0.70°	-58.70°	Non	Reflex	179.00	4.10°	-58.50°	Non
Reflex	83.00	0.70°	-58.70°	Non	Reflex	182.00	3.00°	-58.50°	Oui
Reflex	86.00	0.90°	-58.80°	Non	Reflex	185.00	4.70°	-58.60°	Non
Reflex	89.00	0.80°	-58.70°	Non	Reflex	188.00	4.40°	-58.60°	Non
Reflex	92.00	0.90°	-58.80°	Non	Reflex	191.00	5.30°	-58.50°	Non
Reflex	95.00	0.90°	-58.90°	Non	Reflex	194.00	4.10°	-58.50°	Non
Reflex	98.00	0.90°	-59.00°	Non	Reflex	197.00	5.80°	-58.40°	Non
Reflex	101.00	1.50°	-59.00°	Non	Reflex	200.00	6.20°	-58.30°	Non
Reflex	104.00	1.70°	-59.00°	Non	Reflex	203.00	6.00°	-58.20°	Non
Reflex	107.00	2.30°	-59.00°	Non	Reflex	206.00	6.00°	-58.10°	Non
Reflex	110.00	2.10°	-59.10°	Non	Reflex	209.00	6.20°	-58.00°	Non
Reflex	113.00	2.10°	-59.10°	Non	Reflex	212.00	6.30°	-57.90°	Non
Reflex	116.00	2.10°	-59.10°	Non	Reflex	215.00	6.20°	-57.80°	Non
Reflex	119.00	2.10°	-59.10°	Non	Reflex	218.00	6.40°	-57.70°	Non
Reflex	122.00	2.00°	-59.00°	Non	Reflex	221.00	6.60°	-57.60°	Non
Reflex	125.00	2.10°	-59.00°	Non	Reflex	224.00	6.80°	-57.50°	Non
Reflex	128.00	2.30°	-59.10°	Non	Reflex	227.00	7.00°	-57.30°	Non
Reflex	131.00	2.50°	-59.10°	Non	Reflex	230.00	7.30°	-57.20°	Non
Reflex	134.00	2.70°	-59.10°	Non	Reflex	233.00	7.50°	-57.10°	Non
Reflex	137.00	2.80°	-59.00°	Non	Reflex	236.00	8.20°	-57.20°	Non
Reflex	140.00	2.90°	-59.00°	Non	Reflex	239.00	8.10°	-57.00°	Non
Reflex	143.00	3.10°	-59.00°	Non	Reflex	242.00	8.20°	-57.00°	Non
Reflex	146.00	3.20°	-59.00°	Non	Reflex	245.00	8.80°	-57.00°	Non
Reflex	149.00	3.30°	-59.00°	Non	Reflex	248.00	8.30°	-56.90°	Non
Reflex	152.00	3.60°	-58.90°	Non	Reflex	251.00	8.50°	-56.80°	Non
Reflex	155.00	3.90°	-58.90°	Non	Reflex	254.00	9.30°	-56.80°	Oui
Reflex	158.00	4.00°	-59.00°	Non	Reflex	257.00	7.90°	-56.70°	Non
Reflex	161.00	4.10°	-58.80°	Non	Reflex	260.00	8.20°	-56.60°	Non
Reflex	164.00	4.00°	-58.80°	Non	Reflex	263.00	6.20°	-56.50°	Non
Reflex	167.00	4.20°	-58.70°	Non	Reflex	266.00	6.70°	-56.30°	Non
Reflex	170.00	4.00°	-58.60°	Non	Reflex	269.00	7.20°	-56.30°	Non

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	9.20°	-56.10°	Non	Reflex	371.00	15.00°	-55.00°	Non
Reflex	275.00	10.80°	-56.00°	Non	Reflex	374.00	15.40°	-55.10°	Non
Reflex	278.00	10.20°	-56.00°	Non	Reflex	377.00	15.20°	-55.10°	Non
Reflex	281.00	9.10°	-56.00°	Oui	Reflex	380.00	13.30°	-55.10°	Oui
Reflex	284.00	10.60°	-55.90°	Non	Reflex	383.00	15.30°	-55.10°	Non
Reflex	287.00	10.40°	-55.90°	Non	Reflex	386.00	11.50°	-55.10°	Non
Reflex	290.00	7.20°	-55.90°	Oui	Reflex	389.00	8.40°	-55.10°	Non
Reflex	293.00	10.60°	-55.90°	Non	Reflex	392.00	9.50°	-55.10°	Non
Reflex	296.00	11.30°	-56.00°	Non	Reflex	395.00	14.20°	-55.10°	Non
Reflex	299.00	10.50°	-56.00°	Non	Reflex	398.00	14.60°	-55.10°	Non
Reflex	302.00	11.20°	-55.90°	Non	Reflex	401.00	13.50°	-55.20°	Non
Reflex	305.00	11.50°	-56.00°	Non	Reflex	404.00	8.00°	-55.10°	Oui
Reflex	308.00	10.50°	-56.00°	Non	Reflex	407.00	13.90°	-55.10°	Non
Reflex	311.00	9.70°	-56.00°	Oui	Reflex	410.00	14.60°	-55.10°	Non
Reflex	314.00	12.80°	-55.90°	Non	Reflex	413.00	15.50°	-55.10°	Non
Reflex	317.00	11.90°	-55.90°	Non	Reflex	416.00	16.90°	-55.10°	Non
Reflex	320.00	12.10°	-56.00°	Non	Reflex	419.00	18.30°	-55.20°	Oui
Reflex	323.00	12.20°	-55.80°	Non	Reflex	422.00	16.90°	-55.20°	Non
Reflex	326.00	11.90°	-55.80°	Non	Reflex	425.00	12.70°	-55.20°	Non
Reflex	329.00	12.10°	-55.70°	Non	Reflex	428.00	12.70°	-55.10°	Non
Reflex	332.00	11.60°	-55.70°	Non	Reflex	431.00	14.70°	-55.00°	Non
Reflex	335.00	12.40°	-55.70°	Non	Reflex	434.00	13.80°	-54.90°	Non
Reflex	338.00	12.90°	-55.60°	Non	Reflex	437.00	14.70°	-54.80°	Non
Reflex	341.00	13.20°	-55.60°	Non	Reflex	440.00	15.60°	-54.70°	Non
Reflex	344.00	13.50°	-55.50°	Non	Reflex	443.00	16.00°	-54.70°	Non
Reflex	347.00	13.60°	-55.50°	Non	Reflex	446.00	15.50°	-54.70°	Non
Reflex	350.00	13.50°	-55.40°	Non	Reflex	449.00	15.30°	-54.80°	Non
Reflex	353.00	13.20°	-55.40°	Non	Reflex	452.00	16.70°	-54.80°	Non
Reflex	356.00	13.40°	-55.30°	Non					
Reflex	359.00	13.70°	-55.30°	Non					
Reflex	362.00	13.20°	-55.20°	Non					
Reflex	365.00	14.50°	-55.10°	Non					
Reflex	368.00	14.20°	-55.10°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse					
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)
0.00	4.50	MT						
		<b>Mort-terrain</b>						
4.50	452.00	SY; FIN	4.50	6.00	D019285	1.50	0.108	0.108
		<b>Syénite; Grains fins</b>						
		Syénite à grains fins à moyens avec quelque passage porphyrique à phénocristaux Xmm, sub-autorphe, reparti différentiellement et quelques passage magnétisés.	6.00	7.50	D019286	1.50	0.050	0.050
			7.50	9.00	D019288	1.50	<0.005	0.001
			9.00	10.50	D019289	1.50	<0.005	0.001
			10.50	12.00	D019290	1.50	0.013	0.013
			12.00	13.50	D019291	1.50	0.005	0.005
			13.50	15.00	D019292	1.50	0.010	0.010
			15.00	16.50	D019293	1.50	0.131	0.131
			16.50	18.00	D019294	1.50	0.018	0.018
			18.00	19.50	D019295	1.50	<0.005	0.001
			19.50	21.00	D019296	1.50	0.188	0.188
			21.00	22.50	D019298	1.50	0.564	0.564
			22.50	24.00	D019299	1.50	0.044	0.044
			24.00	25.50	D019300	1.50	0.012	0.012
			25.50	27.00	D019301	1.50	<0.005	0.001
			27.00	28.50	D019302	1.50	<0.005	0.001
			28.50	30.00	D019303	1.50	<0.005	0.001
			30.00	31.50	D019304	1.50	<0.005	0.001
			31.50	33.00	D019305	1.50	<0.005	0.001
			33.00	34.50	D019306	1.50	0.024	0.024
			34.50	36.00	D019308	1.50	0.027	0.027
			36.00	37.50	D019309	1.50	<0.005	0.001
			37.50	39.00	D019310	1.50	<0.005	0.001
			39.00	40.50	D019311	1.50	0.126	0.126
			40.50	42.00	D019312	1.50	0.018	0.018
			42.00	43.50	D019313	1.50	0.023	0.023
			43.50	45.00	D019314	1.50	0.019	0.019
			45.00	46.50	D019315	1.50	0.228	0.228
			46.50	48.00	D019316	1.50	0.032	0.032
			48.00	49.50	D019318	1.50	0.021	0.021
			49.50	51.00	D019319	1.50	0.094	0.094
			51.00	52.50	D019320	1.50	0.345	0.345

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	52.50	54.00	D019321	1.50	0.522		0.522
	54.00	55.50	D019323	1.50	0.099		0.099
	55.50	57.00	D019324	1.50	0.078		0.078
	57.00	58.50	D019325	1.50	0.148		0.148
	58.50	60.00	D019326	1.50	0.078		0.078
	60.00	61.50	D019328	1.50	0.287		0.287
	61.50	63.00	D019329	1.50	0.944		0.944
	63.00	64.50	D019330	1.50	0.396		0.396
	64.50	66.00	D019331	1.50	0.064		0.064
	66.00	67.50	D019332	1.50	0.043		0.043
	67.50	69.00	D019333	1.50	0.110		0.110
	69.00	70.50	D019334	1.50	0.134		0.134
	70.50	72.00	D019335	1.50	0.115		0.115
	72.00	73.50	D019336	1.50	0.169		0.169
	73.50	75.00	D019338	1.50	0.762		0.762
	75.00	76.50	D019339	1.50	1.075		1.075
	76.50	78.00	D019340	1.50	0.720		0.720
	78.00	79.50	D019341	1.50	0.427		0.427
	79.50	81.00	D019342	1.50	0.013		0.013
	81.00	82.50	D019343	1.50	0.031		0.031
	82.50	84.00	D019344	1.50	0.620		0.620
	84.00	85.50	D019345	1.50	0.005		0.005
	85.50	87.00	D019346	1.50	0.012		0.012
	87.00	88.50	D019348	1.50	0.012		0.012
	88.50	90.00	D019349	1.50	0.279		0.279
	90.00	91.50	D019350	1.50	0.449		0.449
	91.50	93.00	D019351	1.50	0.181		0.181
	93.00	94.50	D019352	1.50	0.032		0.032
	94.50	96.00	D019353	1.50	<0.005		0.001
	96.00	97.50	D019354	1.50	<0.005		0.001
	97.50	99.00	D019355	1.50	<0.005		0.001
	99.00	100.50	D019356	1.50	<0.005		0.001
	100.50	102.00	D019358	1.50	0.007		0.007



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	102.00	103.50	D019359	1.50	0.171		0.171
	103.50	105.00	D019360	1.50	0.267		0.267
	105.00	106.50	D019361	1.50	<0.005		0.001
	106.50	108.00	D019363	1.50	0.012		0.012
	108.00	109.00	D019364	1.00	0.158		0.158
	109.00	110.00	D019365	1.00	0.301		0.301
	110.00	111.00	D019366	1.00	0.230		0.230
	111.00	112.50	D019368	1.50	0.116		0.116
	112.50	114.00	D019369	1.50	0.310		0.310
	114.00	115.50	D019370	1.50	1.135		1.135
	115.50	117.00	D019371	1.50	1.405		1.405
	117.00	117.80	D019372	0.80	1.065		1.065
	117.80	119.00	D019373	1.20	0.015		0.015
	119.00	120.50	D019374	1.50	0.549		0.549
	120.50	122.00	D019375	1.50	0.065		0.065
	122.00	123.50	D019376	1.50	1.110		1.110
	123.50	125.00	D019378	1.50	0.005		0.005
	125.00	126.50	D019379	1.50	<0.005		0.001
	126.50	128.00	D019380	1.50	<0.005		0.001
	128.00	129.50	D019381	1.50	<0.005		0.001
	129.50	131.00	D019382	1.50	<0.005		0.001
	131.00	132.50	D019383	1.50	<0.005		0.001
	132.50	134.00	D019384	1.50	<0.005		0.001
	134.00	135.50	D019385	1.50	<0.005		0.001
	135.50	137.00	D019386	1.50	<0.005		0.001
	137.00	138.50	D019388	1.50	<0.005		0.001
	138.50	140.00	D019389	1.50	<0.005		0.001
	140.00	141.50	D019390	1.50	<0.005		0.001
	141.50	143.00	D019391	1.50	<0.005		0.001
	143.00	144.50	D019392	1.50	<0.005		0.001
	144.50	146.00	D019393	1.50	<0.005		0.001
	146.00	147.50	D019394	1.50	<0.005		0.001
	147.50	149.00	D019395	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	149.00	150.50	D019396	1.50	<0.005		0.001
	150.50	152.00	D019398	1.50	<0.005		0.001
	152.00	153.50	D019399	1.50	<0.005		0.001
	153.50	155.00	D019400	1.50	<0.005		0.001
	155.00	156.50	D019401	1.50	<0.005		0.001
	156.50	158.00	D019403	1.50	<0.005		0.001
	158.00	159.00	D019404	1.00	<0.005		0.001
	159.00	160.50	D019405	1.50	<0.005		0.001
	160.50	162.00	D019406	1.50	<0.005		0.001
	162.00	163.00	D019408	1.00	<0.005		0.001
	163.00	164.00	D019409	1.00	<0.005		0.001
	164.00	165.50	D019410	1.50	<0.005		0.001
	165.50	167.00	D019411	1.50	<0.005		0.001
	167.00	168.50	D019412	1.50	<0.005		0.001
	168.50	170.00	D019413	1.50	<0.005		0.001
	170.00	171.50	D019414	1.50	<0.005		0.001
	171.50	173.00	D019415	1.50	0.102		0.102
	173.00	174.50	D019416	1.50	0.067		0.067
	174.50	176.00	D019418	1.50	0.008		0.008
	176.00	177.50	D019419	1.50	<0.005		0.001
	177.50	179.00	D019420	1.50	<0.005		0.001
	179.00	180.50	D019421	1.50	0.152		0.152
	180.50	182.00	D019422	1.50	0.448		0.448
	182.00	183.50	D019423	1.50	0.118		0.118
	183.50	185.00	D019424	1.50	0.170		0.170
	185.00	186.50	D019425	1.50	0.032		0.032
	186.50	188.00	D019426	1.50	0.006		0.006
	188.00	189.50	D019428	1.50	0.005		0.005
	189.50	191.00	D019429	1.50	0.007		0.007
	191.00	192.50	D019430	1.50	0.188		0.188
	192.50	194.00	D019431	1.50	0.012		0.012
	194.00	195.50	D019432	1.50	0.016		0.016
	195.50	197.00	D019433	1.50	0.045		0.045

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	197.00	198.50	D019434	1.50	0.199		0.199
	198.50	200.00	D019435	1.50	1.790		1.790
	200.00	201.50	D019436	1.50	2.100		2.100
	201.50	203.00	D019438	1.50	1.435		1.435
	203.00	204.50	D019439	1.50	0.534		0.534
	204.50	206.00	D019440	1.50	<0.005		0.001
	206.00	207.50	D019441	1.50	<0.005		0.001
	207.50	209.00	D019443	1.50	0.011		0.011
	209.00	210.50	D019444	1.50	0.035		0.035
	210.50	212.00	D019445	1.50	0.029		0.029
	212.00	213.50	D019446	1.50	<0.005		0.001
	213.50	215.00	D019448	1.50	<0.005		0.001
	215.00	216.50	D019449	1.50	0.005		0.005
	216.50	218.00	D019450	1.50	<0.005		0.001
	218.00	219.50	D019451	1.50	<0.005		0.001
	219.50	221.00	D019452	1.50	<0.005		0.001
	221.00	222.50	D019453	1.50	<0.005		0.001
	222.50	224.00	D019454	1.50	0.074		0.074
	224.00	225.50	D019455	1.50	0.033		0.033
	225.50	227.00	D019456	1.50	0.011		0.011
	227.00	228.50	D019458	1.50	0.007		0.007
	228.50	230.00	D019459	1.50	0.088		0.088
	230.00	231.50	D019460	1.50	1.345		1.345
	231.50	233.00	D019461	1.50	0.165		0.165
	233.00	234.50	D019462	1.50	0.006		0.006
	234.50	236.00	D019463	1.50	0.352		0.352
	236.00	237.50	D019464	1.50	0.077		0.077
	237.50	239.00	D019465	1.50	0.058		0.058
	239.00	240.50	D019466	1.50	0.029		0.029
	240.50	242.00	D019468	1.50	0.052		0.052
	242.00	243.50	D019469	1.50	<0.005		0.001
	243.50	245.00	D019470	1.50	<0.005		0.001
	245.00	246.50	D019471	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	246.50	248.00	D019472	1.50	0.008		0.008
	248.00	249.50	D019473	1.50	<0.005		0.001
	249.50	251.00	D019474	1.50	<0.005		0.001
	251.00	252.50	D019475	1.50	0.096		0.096
	252.50	254.00	D019476	1.50	0.621		0.621
	254.00	255.50	D019478	1.50	0.031		0.031
	255.50	257.00	D019479	1.50	0.026		0.026
	257.00	258.50	D019480	1.50	0.223		0.223
	258.50	260.00	D019481	1.50	0.115		0.115
	260.00	261.50	D019483	1.50	0.206		0.206
	261.50	263.00	D019484	1.50	<0.005		0.001
	263.00	264.50	D019485	1.50	<0.005		0.001
	264.50	266.00	D019486	1.50	0.094		0.094
	266.00	267.50	D019488	1.50	<0.005		0.001
	267.50	269.00	D019489	1.50	<0.005		0.001
	269.00	270.50	D019490	1.50	0.018		0.018
	270.50	272.00	D019491	1.50	<0.005		0.001
	272.00	273.50	D019492	1.50	<0.005		0.001
	273.50	275.00	D019493	1.50	<0.005		0.001
	275.00	276.50	D019494	1.50	0.044		0.044
	276.50	278.00	D019495	1.50	0.037		0.037
	278.00	279.50	D019496	1.50	0.040		0.040
	279.50	281.00	D019498	1.50	0.060		0.060
	281.00	282.50	D019499	1.50	0.134		0.134
	282.50	284.00	D019500	1.50	0.079		0.079
	284.00	285.50	D019501	1.50	0.150		0.150
	285.50	287.00	D019503	1.50	0.055		0.055
	287.00	288.50	D019504	1.50	0.038		0.038
	288.50	290.00	D019505	1.50	<0.005		0.001
	290.00	291.50	D019506	1.50	<0.005		0.001
	291.50	293.00	D019508	1.50	<0.005		0.001
	293.00	294.50	D019509	1.50	0.091		0.091
	294.50	296.00	D019510	1.50	0.008		0.008

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	296.00	297.50	D019511	1.50	0.025		0.025
	297.50	299.00	D019512	1.50	<0.005		0.001
	299.00	300.50	D019513	1.50	<0.005		0.001
	300.50	302.00	D019514	1.50	0.008		0.008
	302.00	303.50	D019515	1.50	0.019		0.019
	303.50	305.00	D019516	1.50	0.005		0.005
	305.00	306.50	D019518	1.50	0.006		0.006
	306.50	308.00	D019519	1.50	0.020		0.020
	308.00	309.50	D019520	1.50	<0.005		0.001
	309.50	311.00	D019521	1.50	0.055		0.055
	311.00	312.50	D019522	1.50	0.008		0.008
	312.50	314.00	D019523	1.50	0.010		0.010
	314.00	315.50	D019524	1.50	0.085		0.085
	315.50	317.00	D019525	1.50	0.026		0.026
	317.00	318.50	D019526	1.50	0.089		0.089
	318.50	320.00	D019528	1.50	0.053		0.053
	320.00	321.50	D019529	1.50	<0.005		0.001
	321.50	323.00	D019530	1.50	0.006		0.006
	323.00	324.50	D019531	1.50	0.010		0.010
	324.50	326.00	D019532	1.50	0.029		0.029
	326.00	327.50	D019533	1.50	0.016		0.016
	327.50	329.00	D019534	1.50	<0.005		0.001
	329.00	330.50	D019535	1.50	0.030		0.030
	330.50	332.00	D019536	1.50	0.005		0.005
	332.00	333.50	D019538	1.50	0.090		0.090
	333.50	335.00	D019539	1.50	0.012		0.012
	335.00	336.50	D019540	1.50	0.009		0.009
	336.50	338.00	D019541	1.50	<0.005		0.001
	338.00	339.50	D019543	1.50	0.008		0.008
	339.50	341.00	D019544	1.50	0.036		0.036
	341.00	342.50	D019545	1.50	<0.005		0.001
	342.50	344.00	D019546	1.50	<0.005		0.001
	344.00	345.50	D019548	1.50	0.072		0.072

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	345.50	347.00	D019549	1.50	0.127		0.127
	347.00	348.50	D019550	1.50	0.127		0.127
	348.50	350.00	D019551	1.50	0.180		0.180
	350.00	351.50	D019552	1.50	<0.005		0.001
	351.50	353.00	D019553	1.50	0.054		0.054
	353.00	354.50	D019554	1.50	0.855		0.855
	354.50	356.00	D019555	1.50	0.085		0.085
	356.00	357.50	D019556	1.50	0.299		0.299
	357.50	359.00	D019558	1.50	0.133		0.133
	359.00	360.50	D019559	1.50	0.113		0.113
	360.50	362.00	D019560	1.50	0.023		0.023
	362.00	363.50	D019561	1.50	0.022		0.022
	363.50	365.00	D019562	1.50	0.105		0.105
	365.00	366.50	D019563	1.50	0.075		0.075
	366.50	368.00	D019564	1.50	0.006		0.006
	368.00	369.50	D019565	1.50	0.006		0.006
	369.50	371.00	D019566	1.50	0.717		0.717
	371.00	372.50	D019568	1.50	0.062		0.062
	372.50	374.00	D019569	1.50	0.455		0.455
	374.00	375.50	D019570	1.50	0.248		0.248
	375.50	377.00	D019571	1.50	0.409		0.409
	377.00	378.50	D019572	1.50	0.024		0.024
	378.50	380.00	D019573	1.50	0.172		0.172
	380.00	381.50	D019574	1.50	0.077		0.077
	381.50	383.00	D019575	1.50	0.065		0.065
	383.00	384.50	D019576	1.50	0.401		0.401
	384.50	386.00	D019578	1.50	0.707		0.707
	386.00	387.50	D019579	1.50	0.218		0.218
	387.50	389.00	D019580	1.50	0.070		0.070
	389.00	390.50	D019581	1.50	0.114		0.114
	390.50	392.00	D019583	1.50	0.125		0.125
	392.00	393.50	D019584	1.50	0.136		0.136
	393.50	395.00	D019585	1.50	0.346		0.346

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	395.00	396.50	D019586	1.50	0.259		0.259
	396.50	398.00	D019588	1.50	0.058		0.058
	398.00	399.50	D019589	1.50	0.132		0.132
	399.50	401.00	D019590	1.50	0.140		0.140
	401.00	402.50	D019591	1.50	0.592		0.592
	402.50	404.00	D019592	1.50	0.019		0.019
	404.00	405.50	D019593	1.50	<0.005		0.001
	405.50	407.00	D019594	1.50	<0.005		0.001
	407.00	408.50	D019595	1.50	0.007		0.007
	408.50	410.00	D019596	1.50	0.010		0.010
	410.00	411.50	D019598	1.50	<0.005		0.001
	411.50	413.00	D019599	1.50	0.014		0.014
	413.00	414.50	D019600	1.50	0.074		0.074
	414.50	416.00	D019601	1.50	0.082		0.082
	416.00	417.50	D019602	1.50	0.006		0.006
	417.50	419.00	D019603	1.50	0.118		0.118
	419.00	420.50	D019604	1.50	0.047		0.047
	420.50	422.00	D019605	1.50	0.051		0.051
	422.00	423.50	D019606	1.50	0.217		0.217
	423.50	425.00	D019608	1.50	0.007		0.007
	425.00	426.50	D019609	1.50	0.184		0.184
	426.50	428.00	D019610	1.50	0.486		0.486
	428.00	429.50	D019611	1.50	0.127		0.127
	429.50	431.00	D019612	1.50	0.331		0.331
	431.00	432.50	D019613	1.50	0.304		0.304
	432.50	434.00	D019614	1.50	0.304		0.304
	434.00	435.50	D019615	1.50	0.074		0.074
	435.50	437.00	D019616	1.50	0.259		0.259
	437.00	438.50	D019618	1.50	0.771		0.771
	438.50	440.00	D019619	1.50	0.326		0.326
	440.00	441.50	D019620	1.50	0.507		0.507
	441.50	443.00	D019621	1.50	0.948		0.948
	443.00	444.50	D019623	1.50	0.494		0.494

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	444.50	446.00	D019624	1.50	0.260		0.260
	446.00	447.50	D019625	1.50	0.331		0.331
	447.50	449.00	D019626	1.50	0.017		0.017
	449.00	450.50	D019628	1.50	0.085		0.085
	450.50	452.00	D019629	1.50	0.049		0.049
452.00	Fin du sondage Nombre d'échantillons : 301 Nombre d'échantillons QAQC : 44 Longueur totale échantillonnée : 447.50						



Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
6.00	6.00	D019287	J	0.00	0.797	0.797
19.50	21.00	D019297	D019296	1.50	0.181	0.181
33.00	33.00	D019307	K	0.00	1.085	1.085
46.50	48.00	D019317	D019316	1.50	0.036	0.036
52.50	52.50	D019322	M1	0.00	<0.005	0.001
58.50	58.50	D019327	L	0.00	2.130	2.130
72.00	73.50	D019337	D019336	1.50	0.203	0.203
85.50	85.50	D019347	M	0.00	3.350	3.350
99.00	100.50	D019357	D019356	1.50	<0.005	0.001
105.00	105.00	D019362	M1	0.00	<0.005	0.001
110.00	110.00	D019367	J	0.00	0.819	0.819
122.00	123.50	D019377	D019376	1.50	1.230	1.230
135.50	135.50	D019387	K	0.00	1.065	1.065
149.00	150.50	D019397	D019396	1.50	<0.005	0.001
155.00	155.00	D019402	M1	0.00	<0.005	0.001
160.50	160.50	D019407	L	0.00	2.210	2.210
173.00	174.50	D019417	D019416	1.50	0.026	0.026
186.50	186.50	D019427	M	0.00	3.200	3.200
200.00	201.50	D019437	D019436	1.50	2.010	2.010
206.00	206.00	D019442	M1	0.00	<0.005	0.001
212.00	212.00	D019447	J	0.00	0.771	0.771
225.50	227.00	D019457	D019456	1.50	0.019	0.019
239.00	239.00	D019467	K	0.00	1.070	1.070
252.50	254.00	D019477	D019476	1.50	0.447	0.447
258.50	258.50	D019482	M1	0.00	<0.005	0.001
264.50	264.50	D019487	L	0.00	2.110	2.110
278.00	279.50	D019497	D019496	1.50	0.036	0.036
284.00	284.00	D019502	M1	0.00	<0.005	0.001
290.00	290.00	D019507	J	0.00	0.791	0.791
303.50	305.00	D019517	D019516	1.50	0.010	0.010
317.00	317.00	D019527	K	0.00	1.060	1.060
330.50	332.00	D019537	D019536	1.50	<0.005	0.001
336.50	336.50	D019542	M1	0.00	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
342.50	342.50	D019547	L	0.00	2.130	2.130
356.00	357.50	D019557	D019556	1.50	0.309	0.309
369.50	369.50	D019567	M	0.00	3.160	3.160
383.00	384.50	D019577	D019576	1.50	0.483	0.483
389.00	389.00	D019582	M1	0.00	<0.005	0.001
395.00	395.00	D019587	J	0.00	0.853	0.853
408.50	410.00	D019597	D019596	1.50	0.006	0.006
422.00	422.00	D019607	K	0.00	1.005	1.005
435.50	437.00	D019617	D019616	1.50	0.239	0.239
441.50	441.50	D019622	M1	0.00	<0.005	0.001
447.50	447.50	D019627	L	0.00	2.270	2.270

## Corporation Minière Osisko Div. Exploration

<b>Sondage :</b> <b>BD10-241</b>	Titre minier :	Section :	630200
	Canton :	Niveau :	
	Rang :	Place de travail :	Malartic
Foré par : Bradley et frères	Lot :		
Décrit par : Sylvain SAVADOGO	Du : 2010-05-20	Date de description :	2010-07-08
	Au : 2010-05-26		

Collet

Azimut : 0.00°  
 Plongée : -60.00°  
 Longueur : 374.00 m

UTM

Est	630 199.9
Nord	5 374 401.0
Élévation	286.6

Déviations

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	2.00	0.00°	0.00°	Oui
Reflex	5.00	324.80°	-60.10°	Oui
Reflex	8.00	325.60°	-59.90°	Oui
Reflex	11.00	325.30°	-60.00°	Oui
Reflex	14.00	352.60°	-60.00°	Oui
Reflex	17.00	11.40°	-59.80°	Oui
Reflex	20.00	357.40°	-60.10°	Non
Reflex	23.00	358.00°	-60.10°	Non
Reflex	26.00	358.30°	-60.00°	Non
Reflex	29.00	357.40°	-60.10°	Non
Reflex	32.00	358.20°	-60.10°	Non
Reflex	35.00	358.00°	-60.10°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	38.00	358.30°	-60.00°	Non
Reflex	41.00	358.40°	-60.00°	Non
Reflex	44.00	359.20°	-60.10°	Oui
Reflex	47.00	358.60°	-60.00°	Non
Reflex	50.00	358.80°	-60.10°	Non
Reflex	53.00	0.40°	-60.10°	Oui
Reflex	56.00	358.60°	-60.10°	Non
Reflex	59.00	359.20°	-59.90°	Non
Reflex	62.00	358.10°	-58.90°	Non
Reflex	65.00	0.20°	-60.20°	Oui
Reflex	68.00	358.70°	-60.10°	Non
Reflex	71.00	358.10°	-60.30°	Non

Description

Dimension de la carotte :

NQ

Cimenté : Non

Entreposé : Oui

Corporation Minière Osisko Div. Exploration

Déviation

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	74.00	360.00°	-60.30°	Non
Reflex	77.00	359.90°	-60.30°	Non
Reflex	80.00	359.70°	-60.10°	Non
Reflex	83.00	357.70°	-60.40°	Non
Reflex	86.00	359.00°	-60.40°	Non
Reflex	89.00	0.20°	-60.50°	Non
Reflex	92.00	1.90°	-60.60°	Non
Reflex	95.00	1.60°	-60.60°	Non
Reflex	98.00	5.10°	-60.60°	Oui
Reflex	101.00	0.20°	-60.60°	Non
Reflex	104.00	0.20°	-60.60°	Non
Reflex	107.00	0.40°	-60.60°	Non
Reflex	110.00	0.90°	-60.60°	Non
Reflex	113.00	0.20°	-60.70°	Non
Reflex	116.00	2.40°	-60.60°	Non
Reflex	119.00	2.00°	-60.70°	Non
Reflex	122.00	2.80°	-60.70°	Non
Reflex	125.00	1.40°	-60.60°	Non
Reflex	128.00	1.80°	-60.60°	Non
Reflex	131.00	2.40°	-60.60°	Non
Reflex	134.00	1.00°	-60.60°	Non
Reflex	137.00	1.80°	-60.40°	Non
Reflex	140.00	359.00°	-60.50°	Oui
Reflex	143.00	1.70°	-60.60°	Non
Reflex	146.00	1.90°	-60.50°	Non
Reflex	149.00	1.10°	-60.60°	Non
Reflex	152.00	1.20°	-60.60°	Non
Reflex	155.00	1.40°	-60.70°	Non
Reflex	158.00	3.80°	-60.70°	Oui
Reflex	161.00	2.20°	-60.70°	Non
Reflex	164.00	2.90°	-60.70°	Non
Reflex	167.00	2.30°	-60.80°	Non
Reflex	170.00	1.70°	-60.80°	Non

Type	Profondeur	Azimut	Plongée	Invalide
Reflex	173.00	2.60°	-60.80°	Non
Reflex	176.00	2.50°	-60.80°	Non
Reflex	179.00	3.00°	-60.90°	Non
Reflex	182.00	2.70°	-60.80°	Non
Reflex	185.00	4.80°	-60.90°	Non
Reflex	188.00	4.70°	-60.90°	Non
Reflex	191.00	4.40°	-60.80°	Non
Reflex	194.00	5.50°	-60.80°	Non
Reflex	197.00	3.70°	-60.80°	Oui
Reflex	200.00	4.10°	-60.80°	Non
Reflex	203.00	6.00°	-60.80°	Non
Reflex	206.00	5.60°	-60.90°	Non
Reflex	209.00	6.10°	-60.90°	Non
Reflex	212.00	5.00°	-60.90°	Non
Reflex	215.00	4.20°	-60.80°	Oui
Reflex	218.00	5.40°	-60.90°	Non
Reflex	221.00	5.40°	-60.90°	Non
Reflex	224.00	5.30°	-60.90°	Non
Reflex	227.00	5.30°	-60.90°	Non
Reflex	230.00	5.10°	-60.90°	Non
Reflex	233.00	5.20°	-60.90°	Non
Reflex	236.00	5.20°	-60.80°	Non
Reflex	239.00	5.10°	-60.90°	Non
Reflex	242.00	5.10°	-60.90°	Non
Reflex	245.00	5.00°	-60.80°	Non
Reflex	248.00	5.00°	-60.60°	Non
Reflex	251.00	5.10°	-60.50°	Non
Reflex	254.00	4.90°	-60.50°	Non
Reflex	257.00	5.10°	-60.50°	Non
Reflex	260.00	5.30°	-60.40°	Non
Reflex	263.00	5.20°	-60.40°	Non
Reflex	266.00	5.20°	-60.40°	Non
Reflex	269.00	5.30°	-60.20°	Non

Corporation Minière Osisko Div. Exploration

Déviations

Type	Profondeur	Azimut	Plongée	Invalide	Type	Profondeur	Azimut	Plongée	Invalide
Reflex	272.00	5.00°	-60.00°	Non	Reflex	371.00	5.60°	-58.20°	Non
Reflex	275.00	4.70°	-59.70°	Non	Reflex	374.00	5.70°	-58.30°	Non
Reflex	278.00	4.40°	-59.50°	Non					
Reflex	281.00	4.30°	-59.30°	Non					
Reflex	284.00	4.30°	-59.20°	Non					
Reflex	287.00	4.40°	-59.10°	Non					
Reflex	290.00	4.60°	-58.90°	Non					
Reflex	293.00	4.60°	-58.70°	Non					
Reflex	296.00	4.60°	-58.60°	Non					
Reflex	299.00	4.70°	-58.50°	Non					
Reflex	302.00	4.70°	-58.40°	Non					
Reflex	305.00	4.70°	-58.30°	Non					
Reflex	308.00	4.80°	-58.30°	Non					
Reflex	311.00	4.80°	-58.40°	Non					
Reflex	314.00	5.00°	-58.40°	Non					
Reflex	317.00	5.00°	-58.30°	Non					
Reflex	320.00	5.00°	-58.30°	Non					
Reflex	323.00	5.10°	-58.40°	Non					
Reflex	326.00	5.00°	-58.40°	Non					
Reflex	329.00	5.10°	-58.40°	Non					
Reflex	332.00	5.20°	-58.30°	Non					
Reflex	335.00	5.30°	-58.30°	Non					
Reflex	338.00	5.30°	-58.40°	Non					
Reflex	341.00	5.20°	-58.40°	Non					
Reflex	344.00	5.30°	-58.40°	Non					
Reflex	347.00	5.40°	-58.40°	Non					
Reflex	350.00	5.40°	-58.40°	Non					
Reflex	353.00	5.30°	-58.40°	Non					
Reflex	356.00	5.30°	-58.20°	Non					
Reflex	359.00	5.30°	-58.20°	Non					
Reflex	362.00	5.40°	-58.20°	Non					
Reflex	365.00	5.50°	-58.20°	Non					
Reflex	368.00	5.60°	-58.20°	Non					

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
0.00	11.25	MT <b>Mort-terrain</b> MT							
11.25	236.00	SY; POR <b>Syénite; Porphyrique</b> syénite porphyrique avec de phenocristaux de Fp majoritaire arondis peu hematisé et peu chloriteux; plus ou moins et modérément carbonaté, plus ou moins à modérément hématisé et avec des passages peu à plus ou moins chloriteux et peu sericitique; cristaux de pyrite disséminé dans la matrice et les veinules de Qz-CC; contenant des vQz-CC;	11.25	12.50	D035341	1.25	0.117		0.117
			12.50	14.00	D035342	1.50	<0.005		0.001
			14.00	15.50	D035343	1.50	<0.005		0.001
			15.50	17.00	D035344	1.50	<0.005		0.001
			17.00	18.50	D035345	1.50	<0.005		0.001
			18.50	20.00	D035346	1.50	<0.005		0.001
			20.00	21.50	D035347	1.50	0.017		0.017
			21.50	23.00	D035348	1.50	0.012		0.012
			23.00	24.50	D035349	1.50	0.007		0.007
			24.50	26.00	D035351	1.50	0.016		0.016
			26.00	27.50	D035353	1.50	0.034		0.034
			27.50	29.00	D035354	1.50	0.019		0.019
			29.00	30.50	D035355	1.50	0.028		0.028
			30.50	32.00	D035356	1.50	0.067		0.067
			32.00	33.50	D035357	1.50	0.006		0.006
			33.50	35.00	D035358	1.50	0.020		0.020
			35.00	36.50	D035359	1.50	0.007		0.007
			36.50	38.00	D035361	1.50	<0.005		0.001
			38.00	39.50	D035362	1.50	<0.005		0.001
			39.50	41.00	D035363	1.50	0.005		0.005
			41.00	42.50	D035364	1.50	<0.005		0.001
			42.50	44.00	D035365	1.50	<0.005		0.001
11.25	44.00	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; modérément hématisé;							
44.00	63.50	CB05; CH03; HM03 <b>Carbonaté 5; Chloriteux 3; Hématisé 3</b> modérément carbonaté; plus ou moins chloriteux; peu à plus ou moins hématisé;	44.00	45.50	D035366	1.50	0.007		0.007
			45.50	47.00	D035367	1.50	0.034		0.034
			47.00	48.50	D035368	1.50	<0.005		0.001
			48.50	50.00	D035369	1.50	0.008		0.008
			50.00	51.50	D035371	1.50	<0.005		0.001
			51.50	53.00	D035372	1.50	0.005		0.005

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
63.50	110.00	CB05; HM05 <b>Carbonaté 5; Hématisé 5</b> modérément carbonaté; modérément hématisé;	53.00	54.50	D035373	1.50	<0.005		0.001
			54.50	56.00	D035374	1.50	0.030		0.030
			56.00	57.50	D035375	1.50	0.006		0.006
			57.50	59.00	D035376	1.50	0.018		0.018
			59.00	60.50	D035377	1.50	0.092		0.092
			60.50	62.00	D035378	1.50	0.006		0.006
			62.00	63.50	D035379	1.50	0.012		0.012
			63.50	65.00	D035381	1.50	<0.005		0.001
			65.00	66.50	D035382	1.50	0.005		0.005
			66.50	68.00	D035383	1.50	0.017		0.017
			68.00	69.50	D035384	1.50	0.027		0.027
			69.50	71.00	D035385	1.50	0.005		0.005
			71.00	72.50	D035386	1.50	0.009		0.009
			72.50	74.00	D035387	1.50	<0.005		0.001
			74.00	75.50	D035388	1.50	0.016		0.016
			75.50	77.00	D035389	1.50	0.046		0.046
			77.00	78.50	D035391	1.50	0.144		0.144
			78.50	80.00	D035393	1.50	0.273		0.273
			80.00	81.50	D035394	1.50	2.010		2.010
			81.50	83.00	D035395	1.50	1.695		1.695
			83.00	84.50	D035396	1.50	0.381		0.381
			84.50	86.00	D035397	1.50	0.006		0.006
			86.00	87.50	D035398	1.50	<0.005		0.001
			87.50	89.00	D035399	1.50	<0.005		0.001
			89.00	90.50	D035401	1.50	<0.005		0.001
			90.50	92.00	D035402	1.50	<0.005		0.001
			92.00	93.50	D035403	1.50	<0.005		0.001
			93.50	95.00	D035404	1.50	<0.005		0.001
			95.00	96.50	D035405	1.50	<0.005		0.001
			96.50	98.00	D035406	1.50	0.027		0.027
98.00	99.50	D035407	1.50	0.005		0.005			
99.50	101.00	D035408	1.50	<0.005		0.001			
101.00	102.50	D035409	1.50	<0.005		0.001			

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
110.00	236.00	CB05; HM05; CH03 <b>Carbonaté 5; Hématisé 5; Chloriteux 3</b> modérément carbonaté; modérément hématisé; partiellement peu à plus ou moins hématisé;	102.50	104.00	D035411	1.50	0.011		0.011
			104.00	105.50	D035412	1.50	<0.005		0.001
			105.50	107.00	D035413	1.50	<0.005		0.001
			107.00	108.50	D035414	1.50	<0.005		0.001
			108.50	110.00	D035415	1.50	<0.005		0.001
			110.00	111.50	D035416	1.50	<0.005		0.001
			111.50	113.00	D035417	1.50	<0.005		0.001
			113.00	114.50	D035418	1.50	<0.005		0.001
			114.50	116.00	D035419	1.50	0.005		0.005
			116.00	117.50	D035421	1.50	0.006		0.006
			117.50	119.00	D035422	1.50	<0.005		0.001
			119.00	120.50	D035423	1.50	<0.005		0.001
			120.50	122.00	D035424	1.50	0.011		0.011
			122.00	123.50	D035425	1.50	0.022		0.022
			123.50	125.00	D035426	1.50	0.007		0.007
			125.00	126.50	D035427	1.50	<0.005		0.001
			126.50	128.00	D035428	1.50	<0.005		0.001
			128.00	129.50	D035429	1.50	<0.005		0.001
			129.50	131.00	D035431	1.50	<0.005		0.001
			131.00	132.50	D035433	1.50	0.005		0.005
			132.50	134.00	D035434	1.50	<0.005		0.001
			134.00	135.50	D035435	1.50	0.020		0.020
			135.50	137.00	D035436	1.50	0.009		0.009
			137.00	138.50	D035437	1.50	0.015		0.015
			138.50	140.00	D035438	1.50	0.005		0.005
			140.00	141.50	D035439	1.50	0.012		0.012
141.50	143.00	D035441	1.50	0.008		0.008			
143.00	144.50	D035442	1.50	0.005		0.005			
144.50	146.00	D035443	1.50	0.005		0.005			
146.00	147.50	D035444	1.50	0.009		0.009			
147.50	149.00	D035445	1.50	0.006		0.006			
149.00	150.50	D035446	1.50	<0.005		0.001			
150.50	152.00	D035447	1.50	0.015		0.015			



Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	152.00	153.50	D035448	1.50	<0.005		0.001
	153.50	155.00	D035449	1.50	0.044		0.044
	155.00	156.50	D035451	1.50	0.039		0.039
	156.50	158.00	D035452	1.50	0.013		0.013
	158.00	159.50	D035453	1.50	0.013		0.013
	159.50	161.00	D035454	1.50	0.009		0.009
	161.00	162.50	D035455	1.50	0.010		0.010
	162.50	164.00	D035456	1.50	0.047		0.047
	164.00	165.50	D035457	1.50	0.122		0.122
	165.50	167.00	D035458	1.50	0.033		0.033
	167.00	168.50	D035459	1.50	0.006		0.006
	168.50	170.00	D035461	1.50	<0.005		0.001
	170.00	171.50	D035462	1.50	0.036		0.036
	171.50	173.00	D035463	1.50	0.008		0.008
	173.00	174.50	D035464	1.50	0.048		0.048
	174.50	176.00	D035465	1.50	<0.005		0.001
	176.00	177.50	D035466	1.50	<0.005		0.001
	177.50	179.00	D035467	1.50	0.017		0.017
	179.00	180.50	D035468	1.50	0.006		0.006
	180.50	182.00	D035469	1.50	0.095		0.095
	182.00	183.50	D035471	1.50	0.008		0.008
	183.50	185.00	D035473	1.50	0.012		0.012
	185.00	186.50	D035474	1.50	0.094		0.094
	186.50	188.00	D035475	1.50	0.016		0.016
	188.00	189.50	D035476	1.50	0.029		0.029
	189.50	191.00	D035477	1.50	0.128		0.128
	191.00	192.50	D035478	1.50	0.015		0.015
	192.50	194.00	D035479	1.50	0.083		0.083
	194.00	195.50	D035481	1.50	0.051		0.051
	195.50	197.00	D035482	1.50	0.009		0.009
	197.00	198.50	D035483	1.50	<0.005		0.001
	198.50	200.00	D035484	1.50	0.072		0.072
	200.00	201.50	D035485	1.50	0.024		0.024

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			201.50	203.00	D035486	1.50	<0.005		0.001
			203.00	204.50	D035487	1.50	<0.005		0.001
			204.50	206.00	D035488	1.50	0.076		0.076
			206.00	207.50	D035489	1.50	0.021		0.021
			207.50	209.00	D035491	1.50	0.005		0.005
			209.00	210.50	D035492	1.50	<0.005		0.001
			210.50	212.00	D035493	1.50	<0.005		0.001
			212.00	213.50	D035494	1.50	<0.005		0.001
			213.50	215.00	D035495	1.50	0.006		0.006
			215.00	216.50	D035496	1.50	0.011		0.011
			216.50	218.00	D035497	1.50	0.017		0.017
			218.00	219.50	D035498	1.50	<0.005		0.001
			219.50	221.00	D035499	1.50	<0.005		0.001
			221.00	222.50	D035501	1.50	0.010		0.010
			222.50	224.00	D035502	1.50	0.011		0.011
			224.00	225.50	D035503	1.50	0.025		0.025
			225.50	227.00	D035504	1.50	<0.005		0.001
			227.00	228.50	D035505	1.50	0.007		0.007
			228.50	230.00	D035506	1.50	0.007		0.007
			230.00	231.50	D035507	1.50	<0.005		0.001
			231.50	233.00	D035508	1.50	0.006		0.006
			233.00	234.50	D035509	1.50	<0.005		0.001
			234.50	236.00	D035511	1.50	0.092		0.092
236.00	262.00	BA <b>Basalte 45°</b> Basalte métasomatique (REBA), modérément carbonaté, plus ou moins silicifié, plus ou moins sericitique et peu à plus ou moins chloriteuse, albitisée par endroit; le contact avec la syénite est marqué par une zone de transition syénitique cisailée, modérément carbonaté, peu hématisé, peu chloriteux et peu sericitique; Cristaux fins de pyrite disséminée dans la matrice entre 0,5% et 1%;							
236.00	248.00	CB05; SR03; CH03; SI03 <b>Carbonaté 5; Séricitique 3; Chloriteux 3; Silicifié 3</b> modérément carbonaté; plus ou moins silicifié; peu et plus ou moins chloritisé; plus ou moins sericitique; partiellement albitisé;							

Corporation Minière Osisko Div. Exploration

Description			Analyse									
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)			
236.00	262.00	Py01 <b>Pyrite 1%</b> Cristaux fins de pyrite disséminée dans la matrice entre 0,5% et 1%;	236.00	237.50	D035513	1.50	2.280		2.280			
			237.50	239.00	D035514	1.50	3.530		3.530			
			239.00	240.50	D035515	1.50	1.905		1.905			
			240.50	242.00	D035516	1.50	2.830		2.830			
			242.00	243.50	D035517	1.50	6.010		6.010			
			243.50	245.00	D035518	1.50	9.130		9.130			
			245.00	246.50	D035519	1.50	1.285		1.285			
			246.50	248.00	D035521	1.50	0.156		0.156			
248.00	262.00	SI03; SR03 <b>Silicifié 3; Séricitique 3</b> plus ou moins silicifié; plus ou moins sericitique;	248.00	249.50	D035522	1.50	0.419		0.419			
			249.50	251.00	D035523	1.50	0.205		0.205			
			251.00	252.50	D035524	1.50	0.146		0.146			
			252.50	254.00	D035525	1.50	0.033		0.033			
			254.00	255.50	D035526	1.50	0.191		0.191			
			255.50	257.00	D035527	1.50	0.461		0.461			
			257.00	258.50	D035528	1.50	1.040		1.040			
			258.50	260.00	D035529	1.50	0.224		0.224			
			260.00	261.00	D035531	1.00	0.187		0.187			
			261.00	262.00	D035532	1.00	2.530		2.530			
262.00	372.00	BA; COU <b>Basalte 45°; Cousiné</b> Basalte cousiné, partiellement amygdalaire, modérément carbonaté; pyrite disséminé dans la matrice entre 0,2% et 0,5%; contact net entre REBA et CBBA à 262m, 65°AC;	262.00	263.00	D035533	1.00	0.127		0.127			
			263.00	264.50	D035534	1.50	0.064		0.064			
			264.50	266.00	D035535	1.50	0.007		0.007			
			266.00	267.50	D035536	1.50	0.015		0.015			
			267.50	269.00	D035537	1.50	0.043		0.043			
			269.00	270.50	D035538	1.50	0.081		0.081			
			270.50	272.00	D035539	1.50	0.029		0.029			
			272.00	273.50	D035541	1.50	0.015		0.015			
			273.50	275.00	D035542	1.50	<0.005		0.001			
			275.00	276.50	D035543	1.50	<0.005		0.001			
			276.50	278.00	D035544	1.50	<0.005		0.001			
			262.00	374.00	CB05 <b>Carbonaté 5</b> plus ou moins et modérément carbonaté;	262.00	263.00	D035533	1.00	0.127		0.127
						263.00	264.50	D035534	1.50	0.064		0.064
264.50	266.00	D035535				1.50	0.007		0.007			
266.00	267.50	D035536				1.50	0.015		0.015			
267.50	269.00	D035537				1.50	0.043		0.043			
269.00	270.50	D035538				1.50	0.081		0.081			
270.50	272.00	D035539				1.50	0.029		0.029			
272.00	273.50	D035541				1.50	0.015		0.015			

Corporation Minière Osisko Div. Exploration

Description	Analyse						
	De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
	278.00	279.50	D035545	1.50	<0.005		0.001
	279.50	281.00	D035546	1.50	<0.005		0.001
	281.00	282.50	D035547	1.50	<0.005		0.001
	282.50	284.00	D035548	1.50	0.069		0.069
	284.00	285.50	D035549	1.50	0.777		0.777
	285.50	287.00	D035551	1.50	0.188		0.188
	287.00	288.50	D035553	1.50	<0.005		0.001
	288.50	290.00	D035554	1.50	<0.005		0.001
	290.00	291.50	D035555	1.50	0.137		0.137
	291.50	293.00	D035556	1.50	<0.005		0.001
	293.00	294.50	D035557	1.50	<0.005		0.001
	294.50	296.00	D035558	1.50	<0.005		0.001
	296.00	297.50	D035559	1.50	<0.005		0.001
	297.50	299.00	D035561	1.50	<0.005		0.001
	299.00	300.50	D035562	1.50	<0.005		0.001
	300.50	302.00	D035563	1.50	<0.005		0.001
	302.00	303.50	D035564	1.50	<0.005		0.001
	303.50	305.00	D035565	1.50	<0.005		0.001
	305.00	306.50	D035566	1.50	<0.005		0.001
	306.50	308.00	D035567	1.50	<0.005		0.001
	308.00	309.50	D035568	1.50	<0.005		0.001
	309.50	311.00	D035569	1.50	<0.005		0.001
	311.00	312.50	D035571	1.50	<0.005		0.001
	312.50	314.00	D035572	1.50	<0.005		0.001
	314.00	315.50	D035573	1.50	<0.005		0.001
	315.50	317.00	D035574	1.50	<0.005		0.001
	317.00	318.50	D035575	1.50	<0.005		0.001
	318.50	320.00	D035576	1.50	<0.005		0.001
	320.00	321.50	D035577	1.50	<0.005		0.001
	321.50	323.00	D035578	1.50	<0.005		0.001
	323.00	324.50	D035579	1.50	<0.005		0.001
	324.50	326.00	D035581	1.50	<0.005		0.001
	326.00	327.50	D035582	1.50	<0.005		0.001

Corporation Minière Osisko Div. Exploration

Description			Analyse						
			De	À	Numéro	Longueur	Au (AA) (ppm)	Grav22 (ppm)	Au (final) (g/t)
			327.50	329.00	D035583	1.50	<0.005		0.001
			329.00	330.50	D035584	1.50	<0.005		0.001
			330.50	332.00	D035585	1.50	<0.005		0.001
			332.00	333.50	D035586	1.50	<0.005		0.001
			333.50	335.00	D035587	1.50	<0.005		0.001
			335.00	336.50	D035588	1.50	<0.005		0.001
			336.50	338.00	D035589	1.50	<0.005		0.001
			338.00	339.50	D035591	1.50	<0.005		0.001
			339.50	341.00	D035593	1.50	<0.005		0.001
			341.00	342.50	D035594	1.50	<0.005		0.001
			342.50	344.00	D035595	1.50	<0.005		0.001
			344.00	345.50	D035596	1.50	<0.005		0.001
			345.50	347.00	D035597	1.50	<0.005		0.001
			347.00	348.50	D035598	1.50	<0.005		0.001
			348.50	350.00	D035599	1.50	<0.005		0.001
			350.00	351.50	D035601	1.50	<0.005		0.001
			351.50	353.00	D035602	1.50	<0.005		0.001
			353.00	354.50	D035603	1.50	<0.005		0.001
			354.50	356.00	D035604	1.50	<0.005		0.001
356.00	368.00	Py03 <b>Pyrite 3%</b> cristaux grossiers de pyrite disséminé entre 0,2% à 0,8% dans la matrice;	356.00	357.50	D035605	1.50	<0.005		0.001
			357.50	359.00	D035606	1.50	<0.005		0.001
			359.00	360.50	D035607	1.50	<0.005		0.001
			360.50	362.00	D035608	1.50	<0.005		0.001
			362.00	363.50	D035609	1.50	<0.005		0.001
			363.50	365.00	D035611	1.50	<0.005		0.001
			365.00	366.50	D035612	1.50	<0.005		0.001
			366.50	368.00	D035613	1.50	<0.005		0.001
			368.00	369.50	D035614	1.50	<0.005		0.001
			369.50	371.00	D035615	1.50	<0.005		0.001
			371.00	372.50	D035616	1.50	<0.005		0.001
372.00	374.00	GA; MTY <b>Gabbro 30°; Grains moyens</b> gabbro avec des grains moyens de FP (20%); contenant quelques vQz; fin cristaux de pyrite disséminé dans la matrice à 0,2%;	372.50	374.00	D035617	1.50	<0.005		0.001

374.00

Fin du sondage

Nombre d'échantillons : 243

Nombre d'échantillons QAQC : 34

Longueur totale échantillonnée : 362.75

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
23.00	23.00	D035350	J	0.00	0.771	0.771
24.50	24.50	D035352	M1	0.00	0.005	0.005
35.00	36.50	D035360	D035359	1.50	0.005	0.005
48.50	48.50	D035370	K	0.00	0.703	0.703
62.00	63.50	D035380	D035379	1.50	0.009	0.009
75.50	75.50	D035390	L	0.00	2.110	2.110
77.00	77.00	D035392	M1	0.00	<0.005	0.001
87.50	89.00	D035400	D035399	1.50	<0.005	0.001
101.00	101.00	D035410	M	0.00	3.130	3.130
114.50	116.00	D035420	D035419	1.50	<0.005	0.001
128.00	128.00	D035430	J	0.00	0.757	0.757
129.50	129.50	D035432	M1	0.00	<0.005	0.001
140.00	141.50	D035440	D035439	1.50	0.010	0.010
153.50	153.50	D035450	K	0.00	1.100	1.100
167.00	168.50	D035460	D035459	1.50	<0.005	0.001
180.50	180.50	D035470	L	0.00	2.230	2.230
182.00	182.00	D035472	M1	0.00	<0.005	0.001
192.50	194.00	D035480	D035479	1.50	0.074	0.074
206.00	206.00	D035490	M	0.00	3.040	3.040
219.50	221.00	D035500	D035499	1.50	<0.005	0.001
233.00	233.00	D035510	J	0.00	0.745	0.745
234.50	234.50	D035512	M1	0.00	0.007	0.007
245.00	246.50	D035520	D035519	1.50	1.410	1.410
258.50	258.50	D035530	K	0.00	1.040	1.040
270.50	272.00	D035540	D035539	1.50	0.033	0.033
284.00	284.00	D035550	L	0.00	2.150	2.150
285.50	285.50	D035552	M1	0.00	<0.005	0.001
296.00	297.50	D035560	D035559	1.50	<0.005	0.001
309.50	309.50	D035570	M	0.00	3.100	3.100
323.00	324.50	D035580	D035579	1.50	<0.005	0.001
336.50	336.50	D035590	J	0.00	0.656	0.656
338.00	338.00	D035592	M1	0.00	<0.005	0.001
348.50	350.00	D035600	D035599	1.50	<0.005	0.001

Corporation Minière Osisko Div. Exploration

QAQC

De	À	Numéro	Référence	Longueur	Au (AA) (ppm)	Au (final) (g/t)
362.00	362.00	D035610	K	0.00	1.110	1.110