

# GM 29135

CONCENTRATION OF SPODUMENE FROM VAL D'OR

Documents complémentaires

*Additional Files*



Licence



*Licence*

Cette première page a été ajoutée  
au document et ne fait pas partie du  
rapport tel que soumis par les auteurs.

Énergie et Ressources  
naturelles

Québec 

Industrial Confidential

CANADA

DEPARTMENT OF ENERGY, MINES AND RESOURCES

OTTAWA

MINES BRANCH INVESTIGATION REPORT

IR 73-53

September 1973

CONCENTRATION OF SPODUMENE FROM VAL D'OR, QUEBEC

(PROJECT MP-IM-7105)

by

F. H. Hartman and R. A. Wyman

Mineral Processing Division

Ministère des Richesses Naturelles, Québec	
SERVICE DE LA	
DOCUMENTATION TECHNIQUE	
Date:	26 NOV 1973
No GM:	29135

NOTE: This report relates essentially to the samples as received. The report and any correspondence connected therewith shall not be used in full or in part as publicity or advertising matter.

COPY NO.

Industrial Confidential

Mines Branch Investigation Report IR 73-53

CONCENTRATION OF SPODUMENE FROM VAL D'OR, QUEBEC  
(PROJECT MP-IM-7105)

by

F. H. Hartman\* and R. A. Wyman\*\*

- - -

RESUME

The concentration of spodumene (removing feldspar, quartz, mica, and other iron-bearing minerals by "reverse flotation", as patented by Mines Branch) was tried on ore from Val d'Or, Quebec, supplied by Groupe Minier/SULLIVAN/Mining Group Ltd. who desired a low-iron spodumene concentrate.

Tests run with the original method were not promising. However, a simplified process, using only Armac L-10 (0.4 lb per ton) recovered, without cleaning,

(a) 55% material analysing 5.76%  $\text{Li}_2\text{O}$ ; 0.68%  $\text{Fe}_2\text{O}_3$ ;

23.73%  $\text{Al}_2\text{O}_3$

(b) 49% material analysing 5.75%  $\text{Li}_2\text{O}$ ; 0.60%  $\text{Fe}_2\text{O}_3$ ;

24.00%  $\text{Al}_2\text{O}_3$

Cleaning would increase recovery.

---

\* Research Scientist, and \*\* Head, Industrial Minerals Milling Section, Mineral Processing Division, Mines Branch, Department of Energy, Mines and Resources, Ottawa, Canada.

Industriel Confidentiel

Direction des Mines Rapport d'Investigation IR 73-53

CONCENTRATION DE SPODUMENE DE VAL D'OR, QUEBEC  
(PROJET MP-IM-7105)

par

F. H. Hartman\* et R. A. Wyman\*\*

- - -

RESUME

La concentration du spodumène (par une méthode de "flottation inverse" développée par la Direction des Mines impliquant le déplacement du feldspath, du quartz, du mica ainsi que d'autres minéraux contenant du fer) a été tentée sur un minerai de Val D'Or, Québec, lequel fut soumis par le Groupe Minier Sullivan qui désirait obtenir un concentré de spodumène à basse teneur en fer.

Des essais effectués avec la méthode originale n'ont toutefois pas donné de très bons résultats. Cependant, un procédé simplifié, comportant l'utilisation d'Armac L-10 seulement (0.4 lb/tonne), a permis, sans nettoyage, de récupérer:

- (a) 55% de matériel montrant à l'analyse, 5.76% de  $\text{Li}_2\text{O}$ , 0.68% de  $\text{Fe}_2\text{O}_3$  et 23.73% de  $\text{Al}_2\text{O}_3$ ;
- (b) 49% de matériel montrant à l'analyse, 5.75% de  $\text{Li}_2\text{O}$ , 0.60% de  $\text{Fe}_2\text{O}_3$  et 24.00% de  $\text{Al}_2\text{O}_3$ .

Un nettoyage ultérieur permettrait d'accroître la récupération.

---

\*Rechercheur Scientifique et \*\* Chef, Section de Préparation des Minéraux Industriels, Division du Traitement des Minerais, Direction des Mines, Département de l'Energie, des Mines et des Ressources, Ottawa, Canada.

CONTENTS

	<u>Page</u>
Resume .....	i
French Resume .....	ii
Introduction .....	1
Samples .....	1
Experimental Work .....	2
Magnetic Separation .....	2
Grinding .....	3
Flotation .....	3
Original Reverse Flotation .....	3
Modified Concept of Reverse Flotation .....	8
Discussion .....	12
Low-Iron Spodumene .....	12
Other Aspects .....	13
Summary .....	14
Acknowledgements .....	14
References .....	15

TABLES

<u>No.</u>	<u>Page</u>
1. Screen Analysis of Minus 28-Mesh Head Sample (MPD 71/45) .....	2
2. Wet Magnetic Separation of Minus 28-Mesh Head Sample (MPD 71/45) .....	2
3. Grinding Data .....	3
4. Flotation Tests 1 to 4 .....	5
5. Flotation Tests 5 to 7 .....	6
6. Flotation Tests 9 to 11 .....	7
7. Flotation Tests 12 to 14 .....	9
8. Sink Fractions - Rougher Tails .....	10
9. Flotation Test 15 (Modified Method).....	10
10. Flotation Test 16 (Modified Method) .....	11

## INTRODUCTION

Wyman found (1), patented (2), and published (3) information using a new series of reagents to float quartz, feldspar, and iron-bearing minerals from spodumene ore.

The Mines Branch was asked in July, 1971, by Groupe Minier/SULLIVAN Mining Group Ltd. to try this "reverse flotation" approach on spodumene ore from their Quebec Lithium property. An objective was to produce a low-iron spodumene product. Previous work had indicated that (1) a low-iron material was not easily obtainable (4,5) and (2) some iron was present in the spodumene molecule (6).

The results of the initial test program in this case were not encouraging, so the original process was simplified. After new results had been confirmed, the simple method was tried on the Quebec Lithium sample.

## SAMPLES

A cwt of spodumene ore (MPD 71/38) was received, July 29, 1971, from the Quebec Lithium property, in a drum that was either greasy or oily inside the lid; this was replaced with a 110-pound ore sample (MPD 71/45), received August 23, 1971.

A head sample was prepared by jaw and roll crushing about half the ore to pass 28 mesh. This minimized the production of fines; see the screen analysis in Table 1.

TABLE 1

Screen Analysis of Minus 28-Mesh Head Sample (MPD 71/45)

Tyler Screen Fraction		Weight %	Li <sub>2</sub> O %			
Minus	Plus		Analysis	Distribution		
28	35	8.8	1.88	10.5		
35	48	28.3	1.84	32.9		
48	65	15.8	1.63	16.3		
65	100	12.6	1.39	11.1		
100	150	9.3	1.40	8.3		
150	200	6.6	1.28	5.4		
200		18.6	1.32	15.5		
Heads (calc)		100.0	1.57	100.0	Fe <sub>2</sub> O <sub>3</sub> %	Al <sub>2</sub> O <sub>3</sub> %
Heads (assay)			1.59		0.25	16.67

EXPERIMENTAL WORK

Magnetic Separation

The minus 28-mesh head sample was run through the Jones wet magnetic separator, equipped with high-intensity plates, at 25 amperes (Table 2).

TABLE 2

Wet Magnetic Separation of Minus 28-Mesh Head Sample (MPD 71/45)  
Jones Test 1

Fraction	Weight %	Li <sub>2</sub> O %		Fe <sub>2</sub> O <sub>3</sub> %	
		Analysis	Distribution	Analysis	Distribution
Magnetics	7.1	3.95	17.7	0.93	30.6
Middlings	41.6	1.71	45.0	0.20	38.5
Non-Magnetics	51.3	1.15	37.3	0.13	30.9
Heads (calc)	100.0	1.58	100.0	0.21	100.0
Heads, Assay		1.59		0.25	



### Grinding

The minus 28-mesh head sample was ground wet (50% solids) in a medium-size 8.75 x 9.60-inch-long Abbe mill, the media being 3000 g half-inch burundum "cylpebs". For some tests, the plus 48-mesh fraction in the feed was reduced to minus 48 mesh.

Results of the two grinds are given in Table 3.

TABLE 3

Grinding Data  
Head Sample (MPD 71/45)

Screen Test		2		3	
Duration of Grind		15 minutes		40 minutes	
Feed		minus 48-mesh		minus 28-mesh	
Tyler		Weight	Li <sub>2</sub> O %		Weight
Screen Fractions		%	Analysis	Distribution	%
Minus	Plus				
28	35	-			0.8
35	48	-			1.2
48	65	2.2	3.47	5.2	1.7
65	100	9.2	2.50	15.8	3.6
100	150	21.8	1.28	19.2	9.2
150	200	14.3	1.30	12.8	14.2
200	325	18.6	1.32	16.9	24.5
325		33.9	1.29	30.1	44.8
Heads, Calculated		100.0	1.45	100.0	100.0

### Flotation

#### Original Reverse Flotation

Freshly ground ore was conditioned for one minute in a NaOH-alkaline pulp. The pulp was conditioned with soluble starch for one minute to depress spodumene. A collector, the commercially available acetate salt of B-amine, Armac L-10, was added in one-minute conditioning stages and pine oil was tried

as a frother. Several concentrates were cut, and rougher tails were deslimed before filtering.

In some cases before flotation, the ground ore was deslimed by treating with caustic soda, swirling in a pail, settling, and decanting the fines; for some tests it was passed at 25 amperes through the Jones wet magnetic separator equipped with high-intensity plates.

Mica, quartz, and feldspar floats were attempted.

Flotation was done in a 500-gram Denver Sub-A cell.

Table 4 gives results of four tests on minus 28- and minus 48-mesh feed that had been ground 15 minutes.

Test 4 indicated that in the rougher tails higher-grade spodumene was in the finer sizes. Time of grinding was increased.

Grinding for 20 minutes and screening the rougher tails (Test 5) showed a concentration of  $\text{Li}_2\text{O}$  in the plus 48-mesh fraction.

In Test 6, after a 20-minute grind, plus 65-mesh material was removed by wet screening.

Test 7 was a repeat of Test 6 with grinding time increased to 30 minutes.

Results are shown in Table 5. Only the rougher tails were deslimed.

TABLE 4  
Flotation Tests 1 - 4  
15-minute grind and one-minute conditioning\*

Test	1			2			3			4		
<b>CONDITIONS</b>												
Feed mesh	-28			-48			-48			-48		
Magnetic Separation												
Jones High-Intensity plates	-			-			-			25 amp x 2		
Desliming												
Caustic soda lb/ton	1			1			1			-		
Flotation - Mica												
Caustic soda lb/ton	-			-			1			1		
Armac L-10 lb/ton	-			-			0.8			0.4**		
Flotation - Other												
Caustic soda lb/ton	1			1			-			-		
Soluble starch lb/ton	1.2			1.2			1.2			1.2		
Armac L-10 lb/ton	1.2; 0.4; 0.4			1.2; 0.4; 0.4; 0.4; 0.4			0.4			0.4; 0.4; 0.4; 0.4		
Pine oil lb/ton	-			-			0.1			0.1		
<b>REMARKS</b>	all slimes combined			Slimes 2-Rougher Tails			Conc 1 - Mica fraction Conc 2,3,&4 - Pine oil All slimes combined			Conc 1 - Mica Conc 2 - Pine oil only Rougher Tail only deslimed		
<b>RESULTS</b>												
Fractions	Wt %	Anal	Dist	Wt %	Anal	Dist	Wt %	Anal	Dist	Wt %	Anal	Dist
Magnetics	-	-	-	-	-	-	-	-	-	1.8	3.72	4.3
Slimes 1	20.3	1.08	14.8	16.8	0.27	3.2	28.0	1.16	22.9	-	-	-
Slimes 2 Rougher Tails	-	-	-	1.1	2.44	1.9	-	-	-	1.0	3.16	2.0
Conc 1	14.9	0.24	2.4	0.9	0.38	0.2	0.6	0.52	0.2	2.6	1.30	2.2
Conc 2	17.1	0.27	3.1	8.0	0.21	1.2	31.3	0.17	3.8	2.7	0.94	1.6
Conc 3	8.6	0.74	4.3	23.0	0.23	3.8	8.7	0.28	1.7	31.0	0.25	4.9
Conc 4	-	-	-	11.9	0.59	4.9	4.4	0.50	1.6	33.4	0.55	11.7
Conc 5	-	-	-	3.9	1.84	5.1	-	-	-	10.1	3.83	24.4
Conc 6	-	-	-	-	-	-	-	-	-	1.4	3.79	3.4
Rougher Tails (deslimed)	38.9	2.88	73.4	34.4	3.27	79.7	27.0	3.67	69.8	16.0	4.47	45.5
Heads (calcd)	100.0	1.48	100.0	100.0	1.41	100.0	100.0	1.41	100.0	100.0	1.57	100.0
Rougher Tails, plus 65-mesh	-	-	-	-	-	-	-	-	-	11.1	3.75	9.6
65 to 100-mesh	-	-	-	-	-	-	-	-	-	34.2	3.91	30.9
100 to 150 "	-	-	-	-	-	-	-	-	-	30.6	3.84	27.0
minus 150-mesh	-	-	-	-	-	-	-	-	-	24.1	5.82	32.5
Rougher Tails (calcd)										100.0	4.33	100.0

\* Each addition of reagent

\*\* Plus 0.1 lb/ton Pine oil

TABLE 5

Flotation Tests 5 to 7  
Minus 28-mesh feed, varied grind, one-minute conditioning and no desliming

Test	5			6			7		
<u>CONDITONS</u>									
Duration of grind, minutes	20			20			30		
Magnetic Separation									
Jones Hi-Intensity Plates	25 amp x 2			-					
Flotation									
Caustic soda lb/ton	1			1			1		
Soluble starch lb/ton	1.2			1.2			1.2		
Armac L-10 lb/ton	0.8; 0.4; 0.4; 0.4			0.8; 0.4; 0.4			0.8; 0.4; 0.4		
Pine oil lb/ton	0.1      0.1			0.1      0.1			0.1      0.1		
<u>RESULTS</u>									
Fractions	Wt %	Li <sub>2</sub> O %		Wt %	Li <sub>2</sub> O %		Wt %	Li <sub>2</sub> O %	
		Anal	Dist		Anal	Dist		Anal	Dist
Magnetics	3.5	4.40	10.6	-	-	-	-	-	-
Plus 65-Mesh	-			21.2	2.88	41.7	9.2	4.34	26.6
Slimes	1.2	2.48	1.9	1.8	3.44	4.2	0.6	3.66	1.6
Conc 1	5.6	0.38	1.4	4.9	0.23	0.8	9.4	0.27	1.7
Conc 2	37.2	0.31	7.8	42.3	0.28	8.0	45.9	0.31	9.4
Conc 3	25.0	0.78	13.2	20.8	1.25	17.7	23.7	1.42	22.3
Conc 4	2.7	2.80	5.2	-	-	-	-	-	-
Rougher Tails (deslimed)	24.8	3.57	59.9	9.0	4.51	27.6	11.2	5.15	38.4
Heads, Calculated	100.0	1.48	100.0	100.0	1.47	100.0	100.0	1.50	100.0
Rougher Tails, Plus 48-Mesh	24.7	3.87	28.3						
48 to 65-Mesh	25.0	2.96	21.9						
65 to 100-Mesh	23.0	2.83	19.3						
100 to 150-Mesh	17.3	2.92	15.0						
Minus 150-Mesh	10.0	5.23	15.5						
Rougher Tails, Calculated	100.0	3.37	100.0						

In Tests 9, 10, and 11, minus 28-mesh feed was ground for 35 minutes, the concentrate was cleaned twice, all tails were deslimed and the products combined.

In order to try and float feldspar from quartz in Test 10, the pH of the cleaned concentrate was reduced to about 3 and refloated. Mineralogical examination of the products indicated some separation of spar.

Beneficiation of feldspar was carried a step further in Test 11, in that spar, after flotation from quartz, was cleaned once. All products were deslimed before filtering and the slimes were combined; see Table 6.

TABLE 6

Flotation Tests 9 to 11									
Minus 28-mesh feed, 35-minute grind, one-minute conditioning, and no desliming									
Test	9			10			11		
<u>CONDITIONS</u>									
Flotation									
Caustic soda lb/ton	1			1			1		
Soluble starch lb/ton	1.2			1.2			1.2		
Armac L-10 lb/ton	0.8 + 0.4 + 0.4			0.8 + 0.4 + 0.4			0.8 + 0.4 + 0.4		
Pine oil lb/ton	0.1 + 0.1			0.1 + 0.1			0.1 + 0.1		
<u>REMARKS</u>									
				Spar/Quartz float H <sub>2</sub> SO <sub>4</sub> to pH-3			Spar/Quartz float H <sub>2</sub> SO <sub>4</sub> to pH-3		
<u>RESULTS</u>									
Fractions	Wt %	Li <sub>2</sub> O %		Wt %	Li <sub>2</sub> O %		Wt %	Li <sub>2</sub> O %	
		Anal	Dist		Anal	Dist		Anal	Dist
Slimes	3.0	3.51	8.0	4.1	2.99	9.3	13.9	1.79	16.6
Spar Conc				43.5	0.35	11.7	26.5	0.25	4.4
Spar Cl 1 Tails				-	-	-	19.1	0.18	2.3
Quartz Conc				20.2	0.41	6.4	9.7	0.35	2.3
Conc	65.0	0.32	15.2	-	-	-	-	-	-
Cl 2 Tails	4.7	0.65	2.2	6.6	0.90	4.6	4.4	0.98	2.9
Cl 1 Tails	5.3	1.90	7.3	6.3	1.90	9.2	5.3	1.98	7.0
Rougher Tails(deslimed)	22.0	4.19	67.3	19.3	3.97	58.8	21.1	4.58	64.5
Heads, Calculated	100.0	1.36	100.0	100.0	1.30	100.0	100.0	1.49	100.0

Test 12, 13, and 14 used minus 28-mesh head material and varied the time of grind.

Test 12 was the same as Test 11 but with a 40-minute grind.

In Test 13 a second concentrate was cut after adding more NaOH, soluble starch, Armac L-10, and pine oil; this was not deslimed before filtering. Conditioning time was increased to 2 minutes.

Test 14 repeated the conditions of Test 13 but the time of grind was increased from 30 to 35 minutes.

Results are given in Table 7.

Rougher tails from Tests 13 and 14 were separated by tetrabromoethane (TBE) specific gravity 2.96. Sink fractions were analysed chemically for  $\text{Li}_2\text{O}$  and  $\text{Fe}_2\text{O}_3$  and they were then examined mineralogically (see Table 8).

#### Modified Concept of Reverse Flotation

In a natural pH circuit, L-10 appears to be a highly selective reagent to float feldspar, quartz, and iron-bearing minerals from spodumene. The material must be ground fine for liberation and to allow the collector to lift the gangue. Spodumene that may come over with the froth from excess grinding drops off in early stages of cleaning. The amount of L-10 used is less than in an alkaline circuit. Desliming is not necessary.

In Test 15, the ore was ground for 35 minutes in Ottawa tap water, L-10 was added once, and the froth was cleaned twice. Slimes from all samples were combined before filtering.

In Test 16, time of grind was increased to 40 minutes, and some L-10 added to the first cleaning stage. The rougher tails were passed through the Jones magnetic separator, equipped with high-intensity plates, at 25 amperes. All samples, except the magnetics were deslimed before filtering, and all slimes were combined; see Tables 9 and 10.

TABLE 7

Flotation Tests 12 to 14  
Minus 28-mesh feed, varied grind and conditioning, and no desliming

Test	12				13				14			
<u>CONDITIONS</u>												
Duration of Grind (minutes)	40				30				35			
<u>Flotation</u>												
Conditioning Time min	1				2				2			
Caustic soda lb/ton	1				1				1			
Soluble starch lb/ton	1.2				1.2				1.2			
Armac L-10 lb/ton	0.8 + 0.4 + 0.4				0.8 + 0.4				0.8 + 0.4			
Pine oil lb/ton	0.1 + 0.1				0.1				0.1			
<u>REMARKS</u>												
Concentrate 2: NaOH - 1 lb/ton, soluble starch - 1.2 lb/ton, Armac L-10 - 0.4 + 0.4 + 0.4 lb/ton, Pine oil - 0.1 lb/ton												
Spar/Quartz float: H <sub>2</sub> SO <sub>4</sub> to pH - 3												
<u>RESULTS</u>												
Fractions	Wt	Li <sub>2</sub> O %		Al <sub>2</sub> O <sub>3</sub>	Wt	Li <sub>2</sub> O %		Al <sub>2</sub> O <sub>3</sub>	Wt	Li <sub>2</sub> O %		Al <sub>2</sub> O <sub>3</sub>
	%	Anal	Dist	%	%	Anal	Dist	%	%	Anal	Dist	%
Slimes	13.2	1.66	15.8		18.2	1.02	12.5		10.4	1.55	11.2	-
Spar Conc	22.9	0.32	5.3	16.60	8.9	0.21	1.3	17.10	17.5	0.26	3.2	16.47
Spar Cleaner 1 Tails	25.5	0.28	5.1	14.32	13.3	0.15	1.3	14.17	16.4	0.20	2.3	14.04
Quartz Conc	12.0	0.52	4.5	15.79	16.9	0.13	1.5	13.01	15.1	0.23	2.4	13.78
Cl 2 Tails	6.3	1.78	8.0		4.4	0.41	2.0		4.3	0.74	2.2	15.91
Cl 1 Tails	6.3	3.27	14.8		1.6	1.86	1.2		1.0	2.84	2.0	21.58
Conc 2					9.1	1.26	7.7		5.4	1.92	7.2	-
Rougher Tails (deslimed)	13.8	4.67	46.5		27.6	3.91	72.5		29.9	3.35	69.5	-
Heads, Calculated	100.0	1.39	100.0	-	100.0	1.48	100.0	-	100.0	1.43	100.0	-

Test	% Sinks	Li <sub>2</sub> O % Rougher Tails			Fe <sub>2</sub> O <sub>3</sub> %
		Sinks	Calcd	Analysis	
13	54.4	6.68	3.62	3.91	0.76
14	49.0	6.63	3.24	3.35	0.76

TABLE 9

Minus 28-mesh feed, 35 minute grind, one-minute conditioning, and no desliming

CONDITIONS							
Flotation							
Armac L-10 lb/ton		0.4					
Time of float min		5.5					
REMARKS		All fractions were deslimed before filtering and slimes were combined					
RESULTS		Li <sub>2</sub> O %		Fe <sub>2</sub> O <sub>3</sub> %		Al <sub>2</sub> O <sub>3</sub> %	
Fractions	Wt %	Anal	Dist	Anal	Dist	Anal	Dist
Slimes	11.6	1.50	11.3	0.50	22.1	18.16	12.6
Concentrate	8.0	0.48	2.5	0.31	9.5	16.95	8.1
Cleaner 2 Tails	25.4	0.36	5.9	0.12	11.6	14.49	22.0
Cleaner 1 Tails	40.2	0.96	25.1	0.12	18.4	15.17	36.4
Rougher Tails	14.8	5.76	55.2	0.68	38.4	23.73	20.9
Heads, Calculated	100.0	1.54	100.0	0.26	100.0	16.75	100.0



TABLE 10

Flotation Test 16 (Modified Method)

Minus 28-mesh feed, 40 minute grind, one minute conditioning, and no desliming

<u>CONDITIONS</u>									
Flotation: <u>Rougher</u>									
Armac L-10 lb/ton		0.2 + 0.2							
Minutes of float:		2 3							
: <u>Cleaner 1</u>									
Armac L-10 lb/ton		0 + 0.2							
Minutes of float		2.5 2.5							
Magnetic Separation									
Jones, Hi-Intensity Plates		25 amp x 1							
<u>REMARKS</u>		Rougher Tails magnetically separated. All fractions, except magnetics, deslimed before filtering. Slimes combined.							
<u>RESULTS</u>									
Fractions		Wt %	Li <sub>2</sub> O %		Fe <sub>2</sub> O <sub>3</sub> %		Al <sub>2</sub> O <sub>3</sub> %		
			Anal	Dist	Anal	Dist	Anal	Dist	
Slimes		6.6	1.46	6.4	0.70	19.6	18.93	7.6	
Concentrate		27.9	0.44	8.2	0.16	19.1	15.28	26.2	
Cleaner 2 Tails		47.4	0.74	23.3	0.10	20.2	14.15	41.0	
Cleaner 1 Tails		5.2	3.63	12.7	0.37	8.3	20.73	6.7	
Rougher Tails, magnetics		1.3	6.64	5.5	1.56	8.3	25.32	1.9	
" " , middlings		7.4	5.35	26.5	0.46	14.6	22.84	10.4	
" " , non-magnetics		4.2	6.24	17.4	0.55	9.9	24.08	6.2	
Rougher Tails, Combined		12.9	5.75	49.4	0.60	32.8	24.00	18.5	
Heads, Calculated		100.0	1.50	100.0	0.23	100.0	16.32	100.0	

## DISCUSSION

### Low-Iron Spodumene

The possibility of economically producing a low-iron spodumene by physical beneficiation is not promising.

Nickel (6) concluded that iron is in chemical combination with spodumene, probably as a replacement for aluminum. He also suggested that magnetic susceptibility can generally be related to iron content. This is confirmed in Table 10 where the highest-grade product was the magnetic fraction of the rougher tails that ran 6.64%  $\text{Li}_2\text{O}$ . Minus 28-mesh feed before grinding, when separated magnetically (Table 2), gave a magnetic fraction assaying 3.95%  $\text{Li}_2\text{O}$ , much higher in  $\text{Li}_2\text{O}$  and  $\text{Fe}_2\text{O}_3$  than the non-magnetic material. In Test 4 (Table 4) and Test 5 (Table 5), the magnetics removed after grinding but before flotation ran 3.72%  $\text{Li}_2\text{O}$  and 4.40%  $\text{Li}_2\text{O}$ .

The sink fractions of the heavy liquid separation of rougher tails from Tests 13 and 14 (Table 8) assayed the same in  $\text{Fe}_2\text{O}_3$ , 0.76%, although the 30-minute time of grind in Test 13 gave a weight recovery of 27.6% containing 3.91%  $\text{Li}_2\text{O}$  versus a weight recovery of 29.9% containing 3.35%  $\text{Li}_2\text{O}$  in Test 14 with a 35-minute grind. Mineralogical examination identified no iron minerals as such.

Previous work (4,5) with magnetic separation of spodumene concentrate produced non-magnetic fractions containing between 0.61 and 0.72%  $\text{Fe}_2\text{O}_3$ ; concentrate head sample submitted (5) was 6.10%  $\text{Li}_2\text{O}$ ; 2.15%  $\text{Fe}_2\text{O}_3$ .

Current work, with the modified concept, in Test 15 (Table 9), gave a product with 0.68%  $\text{Fe}_2\text{O}_3$ . Magnetic treatment of the rougher tails in Test 16 (Table 10) only reduced  $\text{Fe}_2\text{O}_3$  content to 0.46% in middlings (5.35%  $\text{Li}_2\text{O}$ , 22.84%  $\text{Al}_2\text{O}_3$ ), and 0.55% in non-magnetics (6.24%  $\text{Li}_2\text{O}$ ; 24.08%  $\text{Al}_2\text{O}_3$ ); the  $\text{Fe}_2\text{O}_3 : \text{Li}_2\text{O}$

ratio suggests iron to be present in the crystal lattice of spodumene.

#### Other Aspects

The modified concept (Tables 9 and 10) in which reverse flotation of feldspar, quartz, mica, and iron-bearing minerals in a natural pH circuit, using Armac L-10, appears to leave behind high-grade spodumene. Selectivity without desliming is sharp, as in Test 15, where a recovery of 55% material, assaying 5.76%  $\text{Li}_2\text{O}$ , is achieved with cleaner 1 tails running 0.96%  $\text{Li}_2\text{O}$ . More careful addition of reagent and using some Armac L-10 in the cleaning operation gave a 49.4% recovery at 5.75%  $\text{Li}_2\text{O}$  and a cleaner 1 product with 12% of the  $\text{Li}_2\text{O}$  present at 3.63%. The economics are good because only 0.4 to 0.6 lb/ton Armac L-10 is required to float the large amount of gangue in a relatively low-grade head sample.

The possibility of a simple separation of feldspar and quartz would require more test work. In Table 7, calculating and allowing for  $\text{Al}_2\text{O}_3$  combined with  $\text{Li}_2\text{O}$  present as spodumene, the spar concentrate contained 15.58%  $\text{Al}_2\text{O}_3$  versus 13.00%  $\text{Al}_2\text{O}_3$  in the quartz concentrate (Test 14); 16.38%  $\text{Al}_2\text{O}_3$  to 12.57%  $\text{Al}_2\text{O}_3$  in quartz (Test 13); 15.51 %  $\text{Al}_2\text{O}_3$  to 14.02%  $\text{Al}_2\text{O}_3$  in quartz (Test 12).

The primary objective to recover a low- $\text{Fe}_2\text{O}_3$ , high- $\text{Li}_2\text{O}$  concentrate was not achieved. Results, however, indicated that a simple, low-cost flotation method is available to upgrade the spodumene. This combined with magnetic separation gave some ore fractions lower in  $\text{Fe}_2\text{O}_3$  than were obtained in earlier work on magnetic separation of concentrates (4,5).

By-products consisting of high-feldspar and possibly quartz can probably be recovered at little extra cost.

### SUMMARY

By a simple reverse flotation system, without magnetic separation, typical spodumene recoveries were:

(a) 55% at 5.76%  $\text{Li}_2\text{O}$ , 0.68%  $\text{Fe}_2\text{O}_3$ , and 23.73%  $\text{Al}_2\text{O}_3$ ;

(b) 49% at 5.75%  $\text{Li}_2\text{O}$ , 0.60%  $\text{Fe}_2\text{O}_3$ , and 24.00%  $\text{Al}_2\text{O}_3$ .

The feed contained 1.59%  $\text{Li}_2\text{O}$ , 0.25%  $\text{Fe}_2\text{O}_3$ , and 16.67  $\text{Al}_2\text{O}_3$ , and the reagent used was 0.4 lb per ton Armac L-10.

Magnetic fractionation of spodumene products gave high  $\text{Li}_2\text{O}$  values with high  $\text{Fe}_2\text{O}_3$  content. This supports previous suppositions (6) that iron is present in the crystal lattice of the spodumene.

### ACKNOWLEDGEMENTS

R. M. Buchanan (Head) and C.H.J. Childe (Technician) analyzed various products by X-ray diffraction. A. D. Kent (Chemist) and S. T. Lepage and G. R. Harrison (Technicians) did chemical analyses and J. H. Colborne (Technician) did the heavy-liquid separations. The excellent test work that checks well throughout and with previous programmes was done by P. R. Lachapelle (Technician).

#### REFERENCES

1. R. A. Wyman, "The Floatability of Twenty-one Non-Metallic Minerals", Technical Bulletin TB 108 (January, 1969), Mines Branch, Department of Energy, Mines and Resources, Ottawa, Canada.
2. R. A. Wyman, "Concentration of Spodumene Using Flotation", U.S. Patent 3,710,934, January 16, 1973.
3. R. A. Wyman, "Solving Industrial Mineral Flotation Problems at the Mines Branch, Ottawa, Canada", AIME Transactions, 250, (September, 1971), 231-236.
4. F. H. Hartman, "Jones Separator Tests on Quebec Lithium Spodumene", Mineral Processing Test Report MPT 61-91, Mines Branch, Department of Energy, Mines and Resources, Ottawa, Canada.
5. F. H. Hartman, "Jones Separator Tests on Quebec Lithium Spodumene", Mineral Processing Test Report MPT 62-4, Mines Branch, Department of Energy, Mines and Resources, Ottawa, Canada.
6. E. H. Nickel, "An Investigation into the Mode of Occurrence of Iron in Green Spodumene from Barraute, Quebec", Investigation Report IR 61-73 (June, 1961), Mines Branch, Department of Energy, Mines and Resources, Ottawa, Canada.